

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287657

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

LEE; Chien-Wei et al.

SEMICONDUCTOR DEVICE STRUCTURE WITH GATE STACK

Abstract

A semiconductor device structure is provided. The semiconductor device structure includes a substrate having a base and a fin structure over the base. The fin structure includes a lower portion, a first nanostructure, and a second nanostructure, and the first nanostructure is between the lower portion and the second nanostructure. The semiconductor device structure includes an isolation structure over the base and surrounding the lower portion. The semiconductor device structure includes a gate stack wrapped around an upper portion of the fin structure. The semiconductor device structure includes a source/drain structure partially embedded in the isolation structure and the lower portion of the fin structure.

Inventors: LEE; Chien-Wei (Kaohsiung City, TW), CHEN; Yen-Ting (Taichung City, TW), LEE; Wei-Yang (Taipei City, TW), LIN; Chia-Pin (Xinpu Township, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 87161189

Assignee: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Appl. No.: 19/217850

Filed: May 23, 2025

Related U.S. Application Data

parent US division 17579833 20220120 parent-grant-document US 12317552 child US 19217850

Publication Classification

Int. Cl.: H10D62/10 (20250101); H10D30/67 (20250101); H10D84/01 (20250101); H10D84/03 (20250101)

U.S. Cl.:

CPC **H10D62/118** (20250101); **H10D30/6713** (20250101); **H10D30/6735** (20250101);
H10D30/6757 (20250101); **H10D62/115** (20250101); **H10D84/0128** (20250101);
H10D84/013 (20250101); **H10D84/0151** (20250101); **H10D84/038** (20250101);

Background/Summary

CROSS REFERENCE [0001] This application is a Divisional of U.S. application Ser. No. 17/579,833, filed on Jan. 20, 2022, the entirety of which is incorporated by reference herein.

BACKGROUND

[0002] The semiconductor integrated circuit (IC) industry has experienced rapid growth. Technological advances in IC materials and design have produced generations of ICs. Each generation has smaller and more complex circuits than the previous generation. However, these advances have increased the complexity of processing and manufacturing ICs.

[0003] In the course of IC evolution, functional density (i.e., the number of interconnected devices per chip area) has generally increased while geometric size (i.e., the smallest component (or line) that can be created using a fabrication process) has decreased. This scaling-down process generally provides benefits by increasing production efficiency and lowering associated costs. Such scaling down has also increased the complexity of processing and manufacturing ICs and, for these advances to be realized, similar developments in IC processing and manufacturing are needed.

[0004] One development in the scaling down process is the use of fin-type field effect transistors (FinFETs). It is desired to further improve the operation of FinFETs, such as by using a gate all around (GAA) transistor structure to increase the efficiency of gate control over the transistor channel.

[0005] However, since feature sizes continue to decrease, fabrication processes continue to become more difficult to perform. Therefore, it is a challenge to form reliable semiconductor devices at smaller and smaller sizes.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0006] Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It should be noted that, in accordance with standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0007] FIGS. **1A-1P** are perspective views of various stages of a process for forming a semiconductor device structure, in accordance with some embodiments.

[0008] FIG. **1J-1** is a cross-sectional view illustrating the semiconductor device structure along a sectional line I-I' in FIG. **1J**, in accordance with some embodiments.

[0009] FIG. **1J-2** is a cross-sectional view illustrating the semiconductor device structure along a sectional line II-II' in FIG. **1J**, in accordance with some embodiments.

[0010] FIG. **1P-1** is a cross-sectional view illustrating the semiconductor device structure along a sectional line **1P-1-1P-1'** in FIG. **1P**, in accordance with some embodiments.

[0011] FIGS. **2A-1** to **2D-1** are cross-sectional views of various stages of a process for forming a semiconductor device structure, in accordance with some embodiments.

[0012] FIGS. **2A-2** to **2D-2** are cross-sectional views of various stages of a process for forming a semiconductor device structure, in accordance with some embodiments.

[0013] FIG. 3A is a perspective view of the semiconductor device structure of FIG. 2D-1, in accordance with some embodiments.

[0014] FIG. 3B is a cross-sectional view illustrating the semiconductor device structure along a sectional line III-III' in FIG. 3A, in accordance with some embodiments.

[0015] FIG. 4 is a perspective view of a semiconductor device structure, in accordance with some embodiments.

[0016] FIG. 5 is a perspective view of a semiconductor device structure, in accordance with some embodiments.

DETAILED DESCRIPTION

[0017] The following disclosure provides many different embodiments, or examples, for implementing different features of the subject matter provided. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0018] Furthermore, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0019] The term “substantially” in the description, such as in “substantially flat” or in “substantially coplanar”, etc., will be understood by the person skilled in the art. In some embodiments the adjective substantially may be removed. Where applicable, the term “substantially” may also include embodiments with “entirely”, “completely”, “all”, etc. The term “substantially” may be varied in different technologies and be in the deviation range understood by the skilled in the art. For example, the term “substantially” may also relate to 90% of what is specified or higher, such as 95% of what is specified or higher, especially 99% of what is specified or higher, including 100% of what is specified, though the present invention is not limited thereto. Furthermore, terms such as “substantially parallel” or “substantially perpendicular” may be interpreted as not to exclude insignificant deviation from the specified arrangement and may include for example deviations of up to 10°. The word “substantially” does not exclude “completely” e.g. a composition which is “substantially free” from Y may be completely free from Y.

[0020] The term “about” may be varied in different technologies and be in the deviation range understood by the skilled in the art. The term “about” in conjunction with a specific distance or size is to be interpreted so as not to exclude insignificant deviation from the specified distance or size. For example, the term “about” may include deviations of up to 10% of what is specified, though the present invention is not limited thereto. The term “about” in relation to a numerical value x may mean $x \pm 5$ or 10% of what is specified, though the present invention is not limited thereto.

[0021] Some embodiments of the disclosure are described. Additional operations can be provided before, during, and/or after the stages described in these embodiments. Some of the stages that are described can be replaced or eliminated for different embodiments. Additional features can be added to the semiconductor device structure. Some of the features described below can be replaced

or eliminated for different embodiments. Although some embodiments are discussed with operations performed in a particular order, these operations may be performed in another logical order.

[0022] The gate all around (GAA) transistor structures may be patterned by any suitable method. For example, the structures may be patterned using one or more photolithography processes, including double-patterning or multi-patterning processes. Generally, double-patterning or multi-patterning processes combine photolithography and self-aligned processes, allowing patterns to be created that have, for example, pitches smaller than what is otherwise obtainable using a single, direct photolithography process. For example, in one embodiment, a sacrificial layer is formed over a substrate and patterned using a photolithography process. Spacers are formed alongside the patterned sacrificial layer using a self-aligned process. The sacrificial layer is then removed, and the remaining spacers may then be used to pattern the GAA structure.

[0023] FIGS. **1A-1P** are perspective views of various stages of a process for forming a semiconductor device structure, in accordance with some embodiments. As shown in FIG. **1A**, a substrate **110** is provided, in accordance with some embodiments. The substrate **110** includes a lower portion **112** and a multilayer structure **114**, in accordance with some embodiments. The multilayer structure **114** is formed over the lower portion **112**, in accordance with some embodiments.

[0024] The lower portion **112** includes, for example, a semiconductor substrate. The semiconductor substrate includes, for example, a semiconductor wafer (such as a silicon wafer) or a portion of a semiconductor wafer. In some embodiments, the lower portion **112** is made of an elementary semiconductor material including silicon or germanium in a single crystal, polycrystal, or amorphous structure.

[0025] In some other embodiments, the lower portion **112** is made of a compound semiconductor, such as silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, an alloy semiconductor, such as SiGe, or GaAsP, or a combination thereof. The lower portion **112** may also include multi-layer semiconductors, semiconductor on insulator (SOI) (such as silicon on insulator or germanium on insulator), or a combination thereof.

[0026] In some embodiments, the lower portion **112** is a device wafer that includes various device elements. In some embodiments, the various device elements are formed in and/or over the lower portion **112**. The device elements are not shown in figures for the purpose of simplicity and clarity.

[0027] Examples of the various device elements include active devices, passive devices, other suitable elements, or a combination thereof. The active devices may include transistors or diodes (not shown). The passive devices include resistors, capacitors, or other suitable passive devices.

[0028] For example, the transistors may be metal oxide semiconductor field effect transistors (MOSFET), complementary metal oxide semiconductor (CMOS) transistors, bipolar junction transistors (BJT), high-voltage transistors, high-frequency transistors, p-channel and/or n-channel field effect transistors (PFETs/NFETs), etc.

[0029] Various processes, such as front-end-of-line (FEOL) semiconductor fabrication processes, are performed to form the various device elements. The FEOL semiconductor fabrication processes may include deposition, etching, implantation, photolithography, annealing, planarization, one or more other applicable processes, or a combination thereof.

[0030] In some embodiments, isolation features (not shown) are formed in the lower portion **112**. The isolation features are used to define active regions and electrically isolate various device elements formed in and/or over the lower portion **112** in the active regions. In some embodiments, the isolation features include shallow trench isolation (STI) features, local oxidation of silicon (LOCOS) features, other suitable isolation features, or a combination thereof.

[0031] The multilayer structure **114** is also referred to a super lattice structure or a super lattice epitaxial growth structure, in accordance with some embodiments. The multilayer structure **114** includes sacrificial layers **114a'**, a thick sacrificial layer **114al**, and channel layers **114b'**, in

accordance with some embodiments. The thick sacrificial layer **114a1** is over the sacrificial layers **114a'** and the channel layers **114b'**, in accordance with some embodiments.

[0032] The thick sacrificial layer **114a1** is thicker than the sacrificial layer **114a'**, in accordance with some embodiments. The thick sacrificial layer **114a1** is thicker than the channel layer **114b'**, in accordance with some embodiments. The thick sacrificial layer **114a1** and the sacrificial layer **114a'** are used to reserve a space for a metal gate stack formed in the subsequent process, in accordance with some embodiments.

[0033] The sacrificial layers **114a'** and the channel layers **114b'** are alternately arranged as illustrated in FIG. **1A**, in accordance with some embodiments. It should be noted that, for the sake of simplicity, FIG. **1A** shows three layers of the sacrificial layers **114a'** and three layers of the channel layers **114b'** for illustration, but does not limit the invention thereto. In some embodiments, the number of the sacrificial layers **114a'** or the channel layers **114b'** is between 2 and 10.

[0034] The sacrificial layers **114a'** and the thick sacrificial layer **114a1** are made of a same first material, such as a first semiconductor material, in accordance with some embodiments. The channel layers **114b'** are made of a second material, such as a second semiconductor material, in accordance with some embodiments.

[0035] The first material is different from the second material, in accordance with some embodiments. The first material has an etch selectivity with respect to the second material, in accordance with some embodiments. In some embodiments, the sacrificial layers **114a'** and the thick sacrificial layer **114a1** are made of SiGe, and the channel layers **114b'** are made of Si. The atomic percentage of Ge in the sacrificial layers **114a'** or the thick sacrificial layer **114a1** ranges from about 5% to 40%, in accordance with some embodiments.

[0036] In some other embodiments, the sacrificial layers **114a'** or the channel layers **114b'** are made of other materials such as germanium, a compound semiconductor such as silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide, an alloy semiconductor such as GaAsP, AlInAs, AlGaAs, InGaAs, GaInP, and/or GaInAsP, or combinations thereof.

[0037] The channel layers **114b'** and the lower portion **112** are made of the same material such as Si, in accordance with some embodiments. The material of the sacrificial layers **114a'** and the thick sacrificial layer **114a1** is different from the material of the lower portion **112**, in accordance with some embodiments. In some other embodiments, the sacrificial layers **114a'**, the thick sacrificial layer **114a1**, the channel layers **114b'**, and the lower portion **112** are made of different materials, in accordance with some embodiments.

[0038] The sacrificial layers **114a'**, the thick sacrificial layer **114a1**, and the channel layers **114b'** are formed using an epitaxial growth process such as a molecular beam epitaxy (MBE) process, a metal-organic chemical vapor deposition (MOCVD) process, and/or another suitable epitaxial growth process. The epitaxial growth process is performed under about 350° C. to about 950° C. temperature and about 5 Torr to about 25 Torr pressure for about 10 seconds to about 40 seconds, in accordance with some embodiments.

[0039] As shown in FIG. **1A**, a mask layer **120** is formed over the multilayer structure **114**, in accordance with some embodiments. The mask layer **120** is made of an oxide material such as silicon dioxide (SiO₂), a nitride material such as silicon nitride (Si₃N₄), or another suitable material, which is different from the materials of the substrate **110** (or the multilayer structure **114**), in accordance with some embodiments. The mask layer **120** is formed using a deposition process (e.g., a physical vapor deposition process or a chemical vapor deposition process), in accordance with some embodiments.

[0040] As shown in FIG. **1B**, portions of the mask layer **120** are removed to form trenches **122** in the mask layer **120**, in accordance with some embodiments. The trenches **122** pass through the mask layer **120**, in accordance with some embodiments. The removal process includes a photolithography process and an etching process (e.g., a dry etching process), in accordance with

some embodiments.

[0041] As shown in FIG. 1B, portions of the substrate **110** exposed by the trenches **122** are removed through the trenches **122**, in accordance with some embodiments. The removal process forms trenches **111** in the substrate **110**, in accordance with some embodiments.

[0042] After the removal process, the remaining portion of the substrate **110** includes a base **113** and a fin structure **116**, in accordance with some embodiments. The fin structure **116** is over the base **113**, in accordance with some embodiments. The base **113** is formed from the lower portion **112** (as shown in FIG. 1A), in accordance with some embodiments.

[0043] The fin structure **116** includes a lower portion **115** and a portion of the multilayer structure **114**, in accordance with some embodiments. The portion of the multilayer structure **114** includes portions of the sacrificial layers **114a'**, the thick sacrificial layer **114al**, and the channel layers **114b'**, in accordance with some embodiments. The lower portion **115** is formed from the lower portion **112** (as shown in FIG. 1A), in accordance with some embodiments.

[0044] As shown in FIG. 1C, the mask layer **120** is removed, in accordance with some embodiments. As shown in FIG. 1C, a liner layer **132** is conformally formed over sidewalls **116s** of the fin structure **116** and a top surface **113a** of the base **113**, in accordance with some embodiments.

[0045] As shown in FIG. 1C, a dielectric layer **134** is formed over the liner layer **132** and in the trenches **111**, in accordance with some embodiments. The liner layer **132** and the dielectric layer **134** together form an isolation structure **130**, in accordance with some embodiments. The isolation structure **130** surrounds the fin structure **116**, in accordance with some embodiments.

[0046] The liner layer **132** is made of oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride), or another suitable dielectric material, in accordance with some embodiments. The dielectric layer **134** is made of oxide (such as silicon oxide), fluorosilicate glass (FSG), a low-k dielectric material, and/or another suitable dielectric material. In some embodiments, the liner layer **132** and the dielectric layer **134** are made of different materials.

[0047] The removal of the mask layer **120** and the formation of the liner layer **132** and the dielectric layer **134** include: conformally depositing a liner material layer (not shown) over the substrate **110**; depositing a dielectric material layer (not shown) over the liner material layer; and performing a planarization process to remove the liner material layer and the dielectric material layer outside of the trenches **111** and the mask layer **120**, in accordance with some embodiments.

[0048] The liner material layer may be deposited by an atomic layer deposition (ALD) process, a chemical vapor deposition (CVD) process, or another applicable process. The dielectric material layer may be deposited by a chemical vapor deposition process, an atomic layer deposition process, a physical vapor deposition (PVD) process, or another applicable process.

[0049] For the sake of simplicity, FIG. 1D omits depicting the boundary between the liner layer **132** and the dielectric layer **134** and only shows the isolation structure **130**, in accordance with some embodiments. As shown in FIG. 1D, an upper portion of the isolation structure **130** is removed to expose sidewalls **114c** of the multilayer structure **114**, in accordance with some embodiments. The removal process includes an etching process such as a dry etching process or a wet etching process, in accordance with some embodiments.

[0050] As shown in FIG. 1D, a cladding layer **140** is formed over the sidewalls **114c** of the multilayer structure **114**, in accordance with some embodiments. The cladding layer **140** is used to reserve a space for a metal gate stack formed in the subsequent process, in accordance with some embodiments.

[0051] The sacrificial layers **114a'**, the thick sacrificial layer **114al**, and the cladding layer **140** are made of the same first material, in accordance with some embodiments. The channel layers **114b'** are made of a second material, in accordance with some embodiments. The first material is different from the second material, in accordance with some embodiments.

[0052] The cladding layer **140** is made of a semiconductor material such as SiGe, Si, and/or germanium, a compound semiconductor such as silicon carbide, gallium arsenide, gallium

phosphide, indium phosphide, indium arsenide, and/or indium antimonide, an alloy semiconductor such as GaAsP, AlInAs, AlGaAs, InGaAs, GaInP, and/or GaInAsP, or combinations thereof, in accordance with some embodiments.

[0053] The cladding layer **140** is formed using an epitaxial growth process such as a molecular beam epitaxy (MBE) process, a metal-organic chemical vapor deposition (MOCVD) process, and/or another suitable epitaxial growth process.

[0054] As shown in FIG. **1E**, a liner layer **152** is conformally formed over the isolation structure **130**, the cladding layer **140**, and the multilayer structure **114**, in accordance with some embodiments. As shown in FIG. **1E**, a dielectric layer **154** is formed over the liner layer **152** and in the trenches **111**, in accordance with some embodiments. The liner layer **152** and the dielectric layer **154** together form an isolation structure **150**, in accordance with some embodiments.

[0055] The liner layer **152** is made of oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride), or another suitable dielectric material, in accordance with some embodiments. The dielectric layer **154** is made of oxide (such as silicon oxide), fluorosilicate glass (FSG), a low-k dielectric material, and/or another suitable dielectric material. In some embodiments, the liner layer **152** and the dielectric layer **154** are made of different materials.

[0056] The liner layer **152** may be deposited by an atomic layer deposition (ALD) process, a chemical vapor deposition (CVD) process, or another applicable process. The dielectric layer **154** may be deposited by a chemical vapor deposition process, an atomic layer deposition process, a physical vapor deposition (PVD) process, or another applicable process.

[0057] As shown in FIG. **1F**, an upper portion of the isolation structure **150** is removed, in accordance with some embodiments. The removal process includes an etching process such as a dry etching process or a wet etching process, in accordance with some embodiments.

[0058] As shown in FIG. **1G**, dielectric fins **160** are formed over the isolation structure **150** and in the trenches **111**, in accordance with some embodiments. The formation of the dielectric fins **160** includes forming a dielectric layer over the isolation structure **150**, the cladding layer **140**, and the multilayer structure **114** and in the trenches **111**; and removing portions of the dielectric layer outside of the trenches **111**, in accordance with some embodiments. The dielectric layer remaining in the trenches **111** forms the dielectric fins **160**, in accordance with some embodiments.

[0059] The dielectric layer is formed using a deposition process such as a physical vapor deposition process, a chemical vapor deposition process, an atomic layer deposition process, or the like, in accordance with some embodiments. The removal process of the portions of the dielectric layer outside of the trenches **111** includes a planarization process such as a chemical mechanical polishing process, in accordance with some embodiments.

[0060] The dielectric fins **160** are made of a dielectric material, such as a high dielectric constant (high-k) material, in accordance with some embodiments. The term “high-k material” means a material having a dielectric constant greater than the dielectric constant of silicon dioxide, in accordance with some embodiments.

[0061] The high-k material includes metal oxides, such as hafnium oxide (HfO₂), hafnium silicon oxide (HfSiO), hafnium silicon oxynitride (HfSiON), hafnium tantalum oxide (HfTaO), hafnium titanium oxide (HfTiO), hafnium zirconium oxide (HfZrO), aluminum oxide, hafnium dioxide-alumina (HfO₂—Al₂O₃) alloy, other suitable high-k dielectric materials, or combinations thereof, in accordance with some embodiments.

[0062] In some other embodiments, the high-k material includes metal nitrides, metal silicates, transition metal-oxides, transition metal-nitrides, transition metal-silicates, oxynitrides of metals, other suitable materials, or combinations thereof.

[0063] As shown in FIG. **1H**, the thick sacrificial layer **114a** and upper portions of the cladding layer **140** are removed, in accordance with some embodiments. After the removal process, a trench **162** is formed between the dielectric fins **160**, in accordance with some embodiments.

[0064] The trench **162** exposes the multilayer structure **114** and the cladding layer **140** thereunder,

in accordance with some embodiments. The removal process includes an etching process such as a wet etching process or a dry etching process, in accordance with some embodiments.

[0065] As shown in FIG. 11, gate stacks **170** are formed over the dielectric fins **160**, the multilayer structure **114**, and the cladding layer **140**, in accordance with some embodiments. As shown in FIG. 11, mask layers M1 and M2 are formed over the gate stacks **170**, in accordance with some embodiments. The mask layer M1 is between the mask layer M2 and the gate stacks **170**, in accordance with some embodiments.

[0066] Each gate stack **170** includes a gate dielectric layer **172** and a gate electrode **174**, in accordance with some embodiments. The gate electrode **174** is over the gate dielectric layer **172**, in accordance with some embodiments. The mask layer M1 has strip portions M1s, in accordance with some embodiments.

[0067] The mask layer M2 has strip portions M2s, in accordance with some embodiments. One of the strip portions M1s covers one of the gate stacks **170**, in accordance with some embodiments. One of the strip portions M2s covers the corresponding one of the strip portions M1s, in accordance with some embodiments.

[0068] The formation of the gate stacks **170** includes conformally forming a gate dielectric material layer (not shown) over the dielectric fins **160**, the multilayer structure **114**, and the cladding layer **140**; forming a gate electrode layer (not shown) over the gate dielectric material layer; forming a first mask material layer (not shown) over the gate electrode layer; forming a second mask material layer (not shown) over the first mask material layer; patterning the first mask material layer and the second mask material layer by a photolithography process and an etching process to form the mask layers M1 and M2, which expose portions of the gate electrode layer; and removing the portions of the gate electrode layer and the gate dielectric material layer exposed by the mask layers M1 and M2, in accordance with some embodiments.

[0069] After the removal process, the remaining gate electrode layer forms the gate electrode **174** of each gate stack **170**, and the remaining gate dielectric material layer forms the gate dielectric layer **172** of each gate stack **170**, in accordance with some embodiments.

[0070] The gate dielectric material layer or the gate dielectric layer **172** is made of an insulating material, such as oxide (e.g., silicon oxide), in accordance with some embodiments. The gate dielectric material layer is formed by a deposition process, such as a chemical vapor deposition (CVD) process, a low-pressure chemical vapor deposition (LPCVD) process, a plasma enhanced chemical vapor deposition (PECVD) process, a high-density plasma chemical vapor deposition (HDPCVD) process, a physical vapor deposition (PVD) process, or another applicable process.

[0071] The gate electrode layer or the gate electrode **174** is made of a semiconductor material (e.g., polysilicon) or a conductive material (e.g., metal or alloy), in accordance with some embodiments. The gate electrode layer is formed by a deposition process, such as a physical vapor deposition (PVD) process, a chemical vapor deposition (CVD) process, or another applicable process, in accordance with some embodiments.

[0072] In some embodiments, the mask layer M1 serves a buffer layer or an adhesion layer that is formed between the underlying gate electrode **174** and the overlying mask layer M2. The mask layer M1 may also be used as an etch stop layer when the mask layer M2 is removed or etched.

[0073] In some embodiments, the mask layer M1 is made of an oxide-containing insulating material (e.g., silicon oxide), a nitride-containing insulating material (e.g., silicon nitride, silicon carbide, silicon oxynitride, silicon oxycarbonitride, or silicon carbonitride), or a metal oxide material (e.g., aluminum oxide).

[0074] In some embodiments, the mask layer M2 is made of an oxide-containing insulating material (e.g., silicon oxide), a nitride-containing insulating material (e.g., silicon nitride, silicon oxynitride, silicon oxycarbonitride, or silicon carbonitride), silicon carbide, or a metal oxide material (e.g., aluminum oxide). The mask layers M1 and M2 are made of different materials, in accordance with some embodiments.

[0075] In some embodiments, the first mask material layer is formed by a deposition process, such as a chemical vapor deposition (CVD) process, a low-pressure chemical vapor deposition (LPCVD) process, a plasma enhanced chemical vapor deposition (PECVD) process, or a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, or another applicable process.

[0076] In some embodiments, the second mask material layer is formed by a deposition process, such as a chemical vapor deposition (CVD) process, a low-pressure chemical vapor deposition (LPCVD) process, a plasma enhanced chemical vapor deposition (PECVD) process, or a high-density plasma chemical vapor deposition (HDPCVD) process, a spin-on process, or another applicable process.

[0077] In some embodiments, the removal process of the portions of the gate electrode layer and the gate dielectric material layer exposed by the mask layers M1 and M2 includes an etching process, such as an anisotropic etching process (e.g., a dry etching process), in accordance with some embodiments.

[0078] FIG. 1J-1 is a cross-sectional view illustrating the semiconductor device structure along a sectional line I-I' in FIG. 1J, in accordance with some embodiments. FIG. 1J-2 is a cross-sectional view illustrating the semiconductor device structure along a sectional line II-II' in FIG. 1J, in accordance with some embodiments.

[0079] As shown in FIGS. 1J, 1J-1, and 1J-2, a spacer **180** is formed over sidewalls of the gate stacks **170** and the mask layers M1 and M2, in accordance with some embodiments. In some embodiments, the spacer **180** is a single-layered structure. In some embodiments, the spacer **180** is a multi-layered structure.

[0080] The spacer **180** is made of an oxide-containing insulating material, such as silicon oxide. In some other embodiments, the spacer **180** is made of a nitride-containing insulating material, such as silicon nitride (SiN), silicon oxynitride (SiON), silicon oxycarbonitride (SiOCN), or silicon carbonitride (SiCN).

[0081] The formation of the spacer **180** includes forming a spacer layer (not shown) over the fin structure **116**, the cladding layer **140**, the dielectric fins **160**, and the mask layers M1 and M2; and removing portions of the spacer layer, in accordance with some embodiments.

[0082] The spacer layer is formed using a deposition process, such as a chemical vapor deposition (CVD) process, an atomic layer deposition (ALD) process, or a physical vapor deposition (PVD) process, in accordance with some embodiments. The removal process includes an etching process, such as an anisotropic etching process (e.g., a dry etching process), in accordance with some embodiments.

[0083] As shown in FIGS. 1J, 1J-1, and 1J-2, the fin structure **116**, the dielectric fins **160**, and the cladding layer **140**, which are not covered by the gate stacks **170** and the spacer **180**, are partially removed, in accordance with some embodiments. After the removal process, the cladding layer **140** remains under the gate stacks **170** and the spacer **180**, in accordance with some embodiments.

[0084] The removal process partially removes the multilayer structure **114** and the lower portion **115**, which are not covered by the gate stacks **170** and the spacer **180**, in accordance with some embodiments. The removal process further partially removes the isolation structure **130**, which is not covered by the gate stacks **170** and the spacer **180**, in accordance with some embodiments. Therefore, the removal process forms recesses R in the lower portion **115** of the fin structure **116** and the isolation structure **130**, which are not covered by the gate stacks **170** and the spacer **180**, in accordance with some embodiments.

[0085] The removal process forms recesses **116a** in the fin structure **116**, in accordance with some embodiments. The multilayer structure **114** is divided into multilayer stacks **114S** by the recesses **116a**, in accordance with some embodiments.

[0086] In each multilayer stack **114S**, the remaining sacrificial layers **114a'** form sacrificial nanostructures **114a**, and the remaining channel layers **114b'** form channel nanostructures **114b**, in

accordance with some embodiments. Each multilayer stack **114S** includes three sacrificial nanostructures **114a** and three channel nanostructures **114b**, in accordance with some embodiments. [0087] The sacrificial nanostructures **114a** and the channel nanostructures **114b** include nanowires and/or nanosheets, in accordance with some embodiments. The thickness **T114a** of the sacrificial nanostructure **114a** ranges from about 1 nm to about 15 nm, in accordance with some embodiments. The thickness **T114b** of the channel nanostructure **114b** ranges from about 1 nm to about 15 nm, in accordance with some embodiments.

[0088] In some embodiments, the thickness **T114a** is substantially equal to the thickness **T114b**. In some embodiments, the thickness **T114a** is less than the thickness **T114b**. In some embodiments, the thickness **T114a** is greater than the thickness **T114b**. The removal process for forming the recesses **116a** includes an etching process, such as an anisotropic etching process (e.g., a dry etching process), in accordance with some embodiments.

[0089] As shown in FIG. **1J-1**, the thickness **T170** of the gate stack **170** ranges from about 80 nm to about 140 nm, in accordance with some embodiments. The thickness **T170** ranges from about 100 nm to about 120 nm, in accordance with some embodiments. The thickness **T114S** of the multilayer stack **114S** ranges from about 40 nm to about 110 nm, in accordance with some embodiments. The thickness **T114S** of the multilayer stack **114S** ranges from about 60 nm to about 90 nm, in accordance with some embodiments.

[0090] As shown in FIGS. **1J** and **1K**, portions of the sacrificial nanostructures **114a** and the cladding layer **140** are removed from sidewalls **S1** of the sacrificial nanostructures **114a** and sidewalls **142** of the cladding layer **140**, in accordance with some embodiments.

[0091] Therefore, the removal process forms recesses **R1** in the multilayer stacks **114S**, in accordance with some embodiments. Each recess **R1** is surrounded by the corresponding sacrificial nanostructure **114a** and the corresponding channel nanostructures **114b**, in accordance with some embodiments.

[0092] As shown in FIG. **1K**, the removal process forms recesses **R2**, in accordance with some embodiments. Each recess **R2** is surrounded by the cladding layer **140**, the corresponding gate stack **170**, the corresponding multilayer stack **114S**, and the isolation structure **150**, in accordance with some embodiments. The recesses **R2** are on opposite sides of the multilayer stack **114S**, in accordance with some embodiments.

[0093] The removal process includes etching processes, such as dry etching processes and wet etching processes, in accordance with some embodiments. In some embodiments, the removal process includes a first dry etching process, a first wet etching process, a second dry etching process, and a second wet etching process, which are performed sequentially.

[0094] The first dry etching process includes a plasma etching process, in accordance with some embodiments. The first dry etching process uses He gas of about 300 sccm to about 2200 sccm, Ar gas of about 80 sccm to about 1100 sccm, and NF.sub.3 gas of about 5 sccm to about 200 sccm under about 0° C. to about 30° C. temperature and about 0.5 Torr to about 15 Torr pressure for about 30 seconds to about 80 seconds, in accordance with some embodiments.

[0095] The first wet etching process uses a dilute hydrofluoric acid (HF) solution, in accordance with some embodiments. The volume percentage concentration of the dilute hydrofluoric acid solution ranges from about 0.5% to about 2%, in accordance with some embodiments.

[0096] The second dry etching process uses He gas of about 300 sccm to about 2200 sccm, Ar gas of about 80 sccm to about 1100 sccm, and NF.sub.3 gas of about 5 sccm to about 200 sccm under about 0° C. to about 30° C. temperature and about 0.5 Torr to about 15 Torr pressure for about 10 seconds to about 50 seconds, in accordance with some embodiments.

[0097] The second wet etching process uses a dilute hydrofluoric acid solution, in accordance with some embodiments. The volume percentage concentration of the dilute hydrofluoric acid solution ranges from about 0.5% to about 2%, in accordance with some embodiments.

[0098] As shown in FIG. **1L**, an inner spacer structure **190** is formed in the recesses **R1** and **R2**, in

accordance with some embodiments. The inner spacer structure **190** is a continuous structure, in accordance with some embodiments. The inner spacer structure **190** is wrapped around the corresponding multilayer stack **114S**, in accordance with some embodiments.

[0099] The inner spacer structure **190** includes inner spacers **192** and **194**, in accordance with some embodiments. The inner spacers **192** are in the recesses **R1** of the multilayer stacks **114S**, in accordance with some embodiments. The inner spacers **194** are in the recesses **R2**, which are surrounded by the cladding layer **140**, the corresponding gate stack **170**, the corresponding multilayer stack **114S**, and the isolation structure **150**, in accordance with some embodiments.

[0100] In some embodiments, the inner spacer structure **190** is made of an oxide-containing insulating material, such as silicon oxide, or a nitride-containing insulating material, such as silicon nitride (SiN), silicon oxynitride (SiON), silicon oxycarbonitride (SiOCN), or silicon carbonitride (SiCN), in accordance with some embodiments.

[0101] The formation of the inner spacer structure **190** includes forming an inner spacer material layer over the spacer **180**, the mask layer **M2**, the dielectric fins **160**, the isolation structure **130**, and the substrate **110** and in the recesses **R1** and **R2**; and removing portions of the inner spacer material layer outside of the recesses **R1** and **R2**, in accordance with some embodiments. The remaining inner spacer material layer forms the inner spacer structure **190**, in accordance with some embodiments.

[0102] The inner spacer material layer is formed using a deposition process such as an atomic layer deposition (ALD) process, a chemical vapor deposition (CVD) process, or another applicable process. The removal process of the portions of the inner spacer material layer outside of the recesses **R1** and **R2** includes an etching process, such as a dry etching process or a wet etching process, in accordance with some embodiments.

[0103] As shown in FIG. **1M**, an undoped semiconductor layer **212** is formed in the recesses **R**, in accordance with some embodiments. The undoped semiconductor layer **212** is used to provide a top surface **212a** without residues coming from the removal process of FIG. **1J**, in accordance with some embodiments. The (clean) top surface **212a** is conducive to form epitaxial structures thereon, in accordance with some embodiments.

[0104] The recesses **R** are filled up with the undoped semiconductor layer **212**, in accordance with some embodiments. The undoped semiconductor layer **212** is partially embedded in the isolation structure **130** and the lower portion **115** of the fin structure **116**, in accordance with some embodiments.

[0105] In some embodiments, the entire top surface **212a** of the undoped semiconductor layer **212** is over a top surface **136** of the isolation structure **130**. The undoped semiconductor layer **212** has a thickness **T212** ranges from about 10 nm to about 30 nm, in accordance with some embodiments. The thickness **T212** ranges from about 20 nm to about 30 nm, in accordance with some embodiments.

[0106] As shown in FIG. **1M**, the nanostructures **114b** include nanostructures **114b1**, **114b2**, and **114b3**, in accordance with some embodiments. The undoped semiconductor layer **212** has a trapezoidal shape, in accordance with some embodiments. The top surface **212a** of the undoped semiconductor layer **212** is a curved surface, such as a convex curved surface, in accordance with some embodiments. The top surface **212a** of the undoped semiconductor layer **212** is a (100) surface, in accordance with some embodiments.

[0107] The undoped semiconductor layer **212** is made of an elementary semiconductor material including silicon or another suitable material in a single crystal, polycrystal, or amorphous structure, in accordance with some embodiments.

[0108] The undoped semiconductor layer **212** is formed using an epitaxial process and an etching process, in accordance with some embodiments. Specifically, the epitaxial process and the etching process are performed simultaneously, in accordance with some embodiments.

[0109] The etching process is performed to remove the epitaxial structure formed over the

sidewalls of the nanostructures **114b1**, **114b2**, and **114b3**, in accordance with some embodiments. The etching process is performed using an etching gas including an HCl gas, in accordance with some embodiments. In the etching process, the flow rate of the HCl gas ranges from about 80 sccm to 130 sccm, in accordance with some embodiments.

[0110] The sidewalls of the nanostructures **114b1**, **114b2**, and **114b3** are (110) surfaces, in accordance with some embodiments. The upper surface **115a** of the lower portion **115** of the fin structure **116** is a (100) surface, in accordance with some embodiments. The undoped semiconductor layer **212** grows from the upper surface **115a** of the lower portion **115** and therefore has the top surface **212a**, which is a (100) surface, in accordance with some embodiments.

[0111] The epitaxial process is performed at high temperature and at low pressure to improve the growth rate of the undoped semiconductor layer **212** with the (100) surface so as to fill the recesses **R** up with the undoped semiconductor layer **212**, in accordance with some embodiments. The process temperature of the epitaxial process ranges from about 700° C. to about 900° C., in accordance with some embodiments. The process temperature of the epitaxial process ranges from about 700° C. to about 800° C., in accordance with some embodiments.

[0112] The process pressure of the epitaxial process ranges from about 5 torr to about 30 torr, in accordance with some embodiments. The process pressure of the epitaxial process ranges from about 5 torr to about 25 torr, in accordance with some embodiments. The process pressure of the epitaxial process ranges from about 5 torr to about 20 torr, in accordance with some embodiments.

[0113] If the undoped semiconductor layer **212** is in direct contact with the inner spacer structure **190**, the growth rate of the undoped semiconductor layer **212** with the (100) surface is decreased, in accordance with some embodiments. Therefore, the top surface **212a** of the undoped semiconductor layer **212** is lower than a bottom surface S.sub.114b1 of the nanostructure **114b1**, in accordance with some embodiments.

[0114] As shown in FIG. 1N, a doped layer **214** is formed over the undoped semiconductor layer **212**, in accordance with some embodiments. The undoped semiconductor layer **212** separates the doped layer **214** from the lower portion **115** of the fin structure **116** and the isolation structure **130**, which prevents the dopants in the doped layer **214** from diffusing into the isolation structure **130**, in accordance with some embodiments. Therefore, the generation of the leakage current between source/drain structures formed subsequently is prevented, and the short circuit between the source/drain structures is prevented, in accordance with some embodiments. Therefore, the drain-induced barrier lowering (DIBL) issue is prevented, in accordance with some embodiments.

[0115] In some embodiments, a top surface **214a** of the doped layer **214** is between a top surface S.sub.A114b1 of the nanostructure **114b1** and a bottom surface S.sub.114b2 of the nanostructure **114b2**. The doped layer **214** is in direct contact with the nanostructure **114b1**, in accordance with some embodiments. The top surface **214a** of the doped layer **214** is a curved surface, such as a convex curved surface, in accordance with some embodiments.

[0116] The thickness **T214** of the doped layer **214** ranges from about 2 nm to about 20 nm, in accordance with some embodiments. The thickness **T214** of the doped layer **214** ranges from about 5 nm to about 15 nm, in accordance with some embodiments. The doped layer **214** is thinner than the undoped semiconductor layer **212**, in accordance with some embodiments.

[0117] In some embodiments, the doped layer **214** is made of a semiconductor material (e.g., silicon germanium) with P-type dopants, such as the Group IIIA element, in accordance with some embodiments. The Group IIIA element includes boron or another suitable material.

[0118] In some other embodiments, the doped layer **214** is made of a semiconductor material (e.g., silicon) with N-type dopants, such as the Group VA element, in accordance with some embodiments. The Group VA element includes phosphor (P), antimony (Sb), or another suitable Group VA material.

[0119] The dopant concentration of the doped layer **214** ranges from about 1×10^{20} atom/cm.³ to about 5×10^{20} atom/cm.³, in accordance with some embodiments. The

doped layer **214** is formed using an epitaxial process, in accordance with some embodiments.

[0120] As shown in FIG. **1O**, a doped layer **216** is formed over the doped layer **214**, in accordance with some embodiments. In one of the recesses **116a** of the fin structure **116**, the undoped semiconductor layer **212**, the doped layer **214**, and the doped layer **216** together form a source/drain structure **210**, in accordance with some embodiments.

[0121] The undoped semiconductor layer **212** separates the doped layer **216** from the isolation structure **130** and the lower portion **115** of the fin structure **116**, which prevents the dopants in the doped layer **216** from diffusing into the isolation structure **130**, in accordance with some embodiments.

[0122] As a result, the generation of the leakage current between the source/drain structures **210** is prevented, and the short circuit between the source/drain structures **210** is prevented, in accordance with some embodiments. Therefore, the drain-induced barrier lowering (DIBL) issue is prevented, in accordance with some embodiments. The yield of the doped layer **216** is improved, in accordance with some embodiments. As a result, the reliability of the semiconductor device structure with the undoped semiconductor layer **212** is improved, in accordance with some embodiments.

[0123] Furthermore, the undoped semiconductor layer **212** is formed using a high temperature and low pressure process, in accordance with some embodiments. The cost of the high temperature and low pressure process is low, and the high temperature and low pressure process can be easily performed, in accordance with some embodiments.

[0124] The thickness **T216** of the doped layer **216** ranges from about 40 nm to about 80 nm, in accordance with some embodiments. The thickness **T216** of the doped layer **216** ranges from about 50 nm to about 70 nm, in accordance with some embodiments. The undoped semiconductor layer **212** is thinner than the doped layer **216**, in accordance with some embodiments.

[0125] The dopant concentration of the doped layer **216** is greater than the dopant concentration of the doped layer **214**, in accordance with some embodiments. In some embodiments, a conductivity of the doped layer **216** is greater than a conductivity of the doped layer **214**. Therefore, the doped layer **216** can well control the channel nanostructures **114b**, in accordance with some embodiments. The conductivity of the doped layer **214** is greater than a conductivity of the undoped semiconductor layer **212**, in accordance with some embodiments.

[0126] In some embodiments, the doped layer **216** is made of a semiconductor material (e.g., silicon germanium) with P-type dopants, such as the Group IIIA element, in accordance with some embodiments. The Group IIIA element includes boron or another suitable material.

[0127] In some other embodiments, the doped layer **216** is made of a semiconductor material (e.g., silicon) with N-type dopants, such as the Group VA element, in accordance with some embodiments. The Group VA element includes phosphor (P), antimony (Sb), or another suitable Group VA material.

[0128] If the doped layer **216** is made of SiGe: B, the Ge concentration of the doped layer **216** ranges from about 40 atom % to about 60 atom %, in accordance with some embodiments. The B concentration of the doped layer **216** ranges from about 9×10^{20} atom/cm.³ to about 21×10^{21} atom/cm.³, in accordance with some embodiments. The doped layer **216** is formed using an epitaxial process, in accordance with some embodiments.

[0129] As shown in FIG. **1O**, the undoped semiconductor layer **212** and the doped layers **214** and **216** have a substantially same width, in accordance with some embodiments. The source/drain structures **210** are formed over the lower portion **115** of the fin structure **116**, in accordance with some embodiments. The source/drain structures **210** are connected to the sidewalls of the channel nanostructures **114b**, in accordance with some embodiments. The source/drain structures **210** are also referred to as stressors, in accordance with some embodiments.

[0130] FIG. **1P-1** is a cross-sectional view illustrating the semiconductor device structure along a sectional line **1P-1-1P-1'** in FIG. **1P**, in accordance with some embodiments. FIG. **2A-1** is a cross-

sectional view illustrating the semiconductor device structure along a sectional line I-I' in FIG. 1P, in accordance with some embodiments. FIG. 2A-2 is a cross-sectional view illustrating the semiconductor device structure along a sectional line II-II' in FIG. 1P, in accordance with some embodiments.

[0131] As shown in FIGS. 1P, 1P-1, and 2A-1, an etch stop layer **220** is formed over the source/drain structures **210**, the dielectric fins **160**, and sidewalls of the spacer **180**, in accordance with some embodiments. The etch stop layer **220** conformally covers the source/drain structures **210**, the dielectric fins **160**, and the sidewalls of the spacer **180**, in accordance with some embodiments.

[0132] The etch stop layer **220** is made of a dielectric material such as a nitride-containing material including silicon nitride (SiN), silicon oxynitride (SiON), or silicon carbonitride (SiCN), in accordance with some embodiments.

[0133] As shown in FIGS. 1P, 1P-1, and 2A-1, a dielectric layer **230** is formed over the etch stop layer **220**, in accordance with some embodiments. The etch stop layer **220** is between the dielectric layer **230** and the source/drain structures **210** to separate the dielectric layer **230** from the source/drain structures **210**, in accordance with some embodiments.

[0134] The dielectric layer **230** is made of an insulating material such as an oxide-containing material including silicon oxide, or a nitride-containing material including silicon nitride, silicon oxynitride, silicon oxycarbonitride, or silicon carbonitride, in accordance with some embodiments.

[0135] As shown in FIGS. 1P, 1P-1, 2A-1, and 2A-2, the mask layers M1 and M2 are removed, in accordance with some embodiments. As shown in FIG. 2A-1, after the removal process, top surfaces **222**, **232**, **182**, and **176** of the etch stop layer **220**, the dielectric layer **230**, the spacer **180**, and the gate stack **170** are substantially level with each other, in accordance with some embodiments. The removal process includes a planarization process such as a chemical mechanical polishing process, in accordance with some embodiments.

[0136] The formation of the etch stop layer **220** and the dielectric layer **230** and the removal process of the mask layers M1 and M2 include forming an etch stop material layer (not shown) over the source/drain structures **210**, the spacer **180**, and the mask layer M2; forming a dielectric material layer over the etch stop material layer; and removing top portions of the etch stop material layer, the dielectric material layer, the spacer **180**, and the gate stack **170** and the mask layers M1 and M2, in accordance with some embodiments.

[0137] After the removal process, the remaining etch stop material layer forms the etch stop layer **220**, and the remaining dielectric material layer forms the dielectric layer **230**, in accordance with some embodiments. The etch stop material layer is formed using a deposition process, such as a chemical vapor deposition process or a physical vapor deposition process, in accordance with some embodiments. The dielectric material layer is formed using a deposition process, such as a chemical vapor deposition process or a physical vapor deposition process, in accordance with some embodiments.

[0138] As shown in FIG. 1P-1, a bottom surface **216a** of the doped layer **216** is higher than a bottom surface **144** of the cladding layer **140**, in accordance with some embodiments. As shown in FIG. 1P, the top surface **216b** of the doped layer **216** is a curved surface, such as a convex curved surface, in accordance with some embodiments.

[0139] As shown in FIG. 1P-1, in some embodiments, a bottom surface **214b** of the doped layer **214** is higher than the bottom surface **144** of the cladding layer **140**. In some embodiments, a bottom surface **212b** of the undoped semiconductor layer **212** is lower than the bottom surface **144** of the cladding layer **140**.

[0140] FIGS. 2A-1 to 2D-1 are cross-sectional views of various stages of a process for forming a semiconductor device structure, in accordance with some embodiments. FIGS. 2A-2 to 2D-2 are cross-sectional views of various stages of a process for forming a semiconductor device structure, in accordance with some embodiments.

[0141] As shown in FIGS. 2B-1 and 2B-2, the gate stacks **170** are removed to form trenches **184** in the spacer **180** and trench **162** between the dielectric fins **160**, in accordance with some embodiments. The removal process includes an etching process, such as a wet etching process or a dry etching process, in accordance with some embodiments.

[0142] As shown in FIGS. 2B-1 and 2B-2, the sacrificial nanostructures **114a** and the cladding layer **140** are removed through the trenches **184** in the spacer **180** and the trench **162** between the dielectric fins **160**, in accordance with some embodiments. As shown in FIG. 2B-1, gaps **G** between the lower portion **115** and the channel nanostructure **114b** and between the channel nanostructures **114b** are formed after removing the sacrificial nanostructures **114a**, in accordance with some embodiments.

[0143] As shown in FIG. 2B-2, through holes **156** are formed in the isolation structure **150** after removing the cladding layer **140**, in accordance with some embodiments. The through holes **156** expose the isolation structure **130** thereunder, in accordance with some embodiments. The removal process includes an etching process, such as a wet etching process or a dry etching process, in accordance with some embodiments.

[0144] As shown in FIGS. 2C-1 and 2C-2, a gate dielectric layer **242** is conformally formed over the channel nanostructures **114b** and the lower portion **115** of the fin structure **116** exposed by the trenches **184** in the spacer **180** and the trench **162** between the dielectric fins **160**, in accordance with some embodiments.

[0145] The gate dielectric layer **242** is further conformally formed over the inner spacers **192**, the spacer **180**, the etch stop layer **220**, the dielectric layer **230**, the dielectric fins **160**, the isolation structure **150**, the isolation structure **130**, and the lower portion **115** of the fin structure **116**, in accordance with some embodiments.

[0146] The gate dielectric layer **242** is made of a dielectric material such as an oxide material (e.g., silicon oxide) or a high-K material, such as HfO_2 , ZrO_2 , HfZrO_2 , or Al_2O_3 , in accordance with some embodiments. The gate dielectric layer **242** is formed using a deposition process, such as a chemical vapor deposition process or a physical vapor deposition process, or another suitable process, in accordance with some embodiments.

[0147] As shown in FIGS. 2C-1 and 2C-2, a work function metal layer **244** is conformally formed over the gate dielectric layer **242** and in the trenches **184** and **162**, in accordance with some embodiments. The work function metal layer **244** is made of titanium-containing material (e.g., TiN or TiSiN) or tantalum-containing material (e.g., TaN), or another suitable conductive material. The work function metal layer **244** is formed using an atomic layer deposition process, a chemical vapor deposition process, a physical vapor deposition process, or another suitable process.

[0148] As shown in FIGS. 2C-1 and 2C-2, a gate electrode layer **246** is formed over the work function metal layer **244**, in accordance with some embodiments. The gate electrode layer **246** is made of W, Co, Al, or another suitable conductive material. The gate electrode layer **246** is formed using a physical vapor deposition process, an atomic layer deposition process, or another suitable process.

[0149] FIG. 3A is a perspective view of the semiconductor device structure of FIG. 2D-1, in accordance with some embodiments. FIG. 2D-1 is a cross-sectional view illustrating the semiconductor device structure along a sectional line I-I' in FIG. 3A, in accordance with some embodiments. FIG. 2D-2 is a cross-sectional view illustrating the semiconductor device structure along a sectional line II-II' in FIG. 3A, in accordance with some embodiments.

[0150] As shown in FIGS. 2D-1, 2D-2, and 3A, portions of the gate dielectric layer **242**, the work function metal layer **244**, and the gate electrode layer **246** outside of the trenches **184** and **162** and top portions of the spacer **180**, the etch stop layer **220**, and the dielectric layer **230** are removed, in accordance with some embodiments.

[0151] After the removal process, in one of the trenches **184** and **162**, the remaining gate dielectric layer **242**, the remaining work function metal layer **244**, and the remaining gate electrode layer **246**

together form a gate stack **240**, in accordance with some embodiments. The gate stack **240** is wrapped around the channel nanostructures **114b**, in accordance with some embodiments. In some embodiments, a portion of the gate stack **240** is between the channel nanostructure **114b** and the lower portion **115**.

[0152] The removal process includes a planarization process such as a chemical mechanical polishing process, in accordance with some embodiments. Therefore, after the removal process, the top surfaces **241**, **182**, **222**, **232**, and **164** of the gate stack **240**, the spacer **180**, the etch stop layer **220**, the dielectric layer **230**, and the dielectric fins **160** are substantially level with each other, in accordance with some embodiments.

[0153] As shown in FIG. 2D-2, each gate stack **240** has an upper portion **241**, sidewall portions **243**, and lower portions **245**, in accordance with some embodiments. The upper portion **241** is over the channel nanostructures **114b**, in accordance with some embodiments. The lower portions **245** are between the channel nanostructures **114b** and between the channel nanostructure **114b** and the lower portion **115**, in accordance with some embodiments.

[0154] As shown in FIG. 2D-2, the sidewall portions **243** are over sidewalls **S114b** of the channel nanostructures **114b**, in accordance with some embodiments. As shown in FIG. 2D-2, the lower portion **245** is wider than the sidewall portion **243**, in accordance with some embodiments.

[0155] In some embodiments, the lower portion **245** of the gate stack **240** is thinner than the channel nanostructure **114b**. In some embodiments, the lower portion **245** of the gate stack **240** and the channel nanostructure **114b** have the same thickness. In some embodiments, the lower portion **245** of the gate stack **240** is thicker than the channel nanostructure **114b**.

[0156] As shown in FIGS. 2D-1 and 2D-2, the inner spacers **192** are under the channel nanostructures **114b** and between the lower portion **245** of the gate stack **240** and the source/drain structures **210**, in accordance with some embodiments. The inner spacer **192** separates the source/drain structures **210** from the lower portions **245** of the gate stack **240**, in accordance with some embodiments.

[0157] As shown in FIG. 2D-1, the inner spacers **192** separate the source/drain structures **210** from the gate stack **240**, in accordance with some embodiments.

[0158] FIG. 3B is a cross-sectional view illustrating the semiconductor device structure along a sectional line III-III' in FIG. 3A, in accordance with some embodiments. As shown in FIG. 3B, a bottom surface **216a** of the doped layer **216** is higher than a bottom surface **241** of the gate stack **240**, in accordance with some embodiments.

[0159] In some embodiments, a bottom surface **214b** of the doped layer **214** is higher than the bottom surface **241** of the gate stack **240**. In some embodiments, a bottom surface **212b** of the undoped semiconductor layer **212** is lower than the bottom surface **241** of the gate stack **240**.

[0160] FIG. 4 is a perspective view of a semiconductor device structure **400**, in accordance with some embodiments. As shown in FIG. 4, the semiconductor device structure **400** is similar to the semiconductor device structure **200** of FIG. 3A, except that the top surface **212a** of the undoped semiconductor layer **212** is a planar surface, in accordance with some embodiments. The top surface **214a** of the doped layer **214** is a planar surface, in accordance with some embodiments. The top surface **216b** of the doped layer **216** is a planar surface, in accordance with some embodiments.

[0161] FIG. 5 is a perspective view of a semiconductor device structure **500**, in accordance with some embodiments. As shown in FIG. 5, the semiconductor device structure **500** is similar to the semiconductor device structure **200** of FIG. 3A, except that the undoped semiconductor layer **212** has a substantially hexagonal shape, in accordance with some embodiments.

[0162] The undoped semiconductor layer **212** has inclined surfaces **212S**, in accordance with some embodiments. The inclined surface **212S** is at a slope (i.e., at an angle θ to a horizontal surface) ranging from about 30° to about 80°, in accordance with some embodiments.

[0163] Processes and materials for forming the semiconductor device structures **400** and **500** may

be similar to, or the same as, those for forming the semiconductor device structure **200** described above. Elements designated by the same reference numbers as those in FIGS. **1A** to **5** have structures and materials that are the same or similar. Therefore, the detailed descriptions thereof will not be repeated herein.

[0164] In accordance with some embodiments, semiconductor device structures and methods for forming the same are provided. The method includes sequentially forming an undoped semiconductor layer and a doped layer over a lower portion of a fin structure and an isolation structure. The undoped semiconductor layer separates the doped layer from the isolation structure, which prevents the dopants in the doped layer from diffusing into the isolation structure. Therefore, the short circuit between source/drain structures is prevented. As a result, the reliability of the semiconductor device structure with the undoped semiconductor layer is improved.

[0165] In accordance with some embodiments, a semiconductor device structure is provided. The semiconductor device structure includes a substrate having a base and a fin structure over the base. The semiconductor device structure includes an isolation structure over the base and surrounding a lower portion of the fin structure. The semiconductor device structure includes a gate stack wrapped around an upper portion of the fin structure. The semiconductor device structure includes a source/drain structure partially embedded in the isolation structure and the lower portion of the fin structure. The source/drain structure has an undoped semiconductor layer and a first doped layer over the undoped semiconductor layer, and the undoped semiconductor layer separates the first doped layer from the isolation structure.

[0166] In accordance with some embodiments, a semiconductor device structure is provided. The semiconductor device structure includes a substrate having a base and a fin structure over the base. The semiconductor device structure includes an isolation structure over the base and surrounding a lower portion of the fin structure. The semiconductor device structure includes a gate stack wrapped around an upper portion of the fin structure. The semiconductor device structure includes a source/drain structure partially embedded in the isolation structure and the lower portion of the fin structure. The source/drain structure has an undoped semiconductor layer and a first doped layer, the first doped layer is over the undoped semiconductor layer, and a first bottom surface of the first doped layer is higher than a second bottom surface of the gate stack.

[0167] In accordance with some embodiments, a method for forming a semiconductor device structure is provided. The method includes providing a substrate having a base and a fin structure over the base. The method includes forming an isolation structure over the base. The isolation structure surrounds a lower portion of the fin structure. The method includes forming a gate stack over the fin structure and the isolation structure. The method includes removing portions of the fin structure and the isolation structure, which are not covered by the gate stack. The removing of the portions of the fin structure and the isolation structure forms a recess in the lower portion of the fin structure and the isolation structure. The method includes forming an undoped semiconductor layer in the recess. The recess is filled up with the undoped semiconductor layer.

[0168] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

- 1.** A semiconductor device structure, comprising: a substrate having a base and a fin structure over the base, wherein the fin structure comprises a lower portion, a first nanostructure, and a second nanostructure, and the first nanostructure is between the lower portion and the second nanostructure; an isolation structure over the base and surrounding the lower portion; a gate stack wrapped around an upper portion of the fin structure; and a source/drain structure partially embedded in the isolation structure and the lower portion of the fin structure, wherein the source/drain structure has an undoped semiconductor layer and a first doped layer over the undoped semiconductor layer, the undoped semiconductor layer separates the first doped layer from the isolation structure, and a topmost portion of the undoped semiconductor layer is lower than a first bottom surface of the first nanostructure.
- 2.** The semiconductor device structure as claimed in claim 1, wherein an entire top surface of the undoped semiconductor layer is over a top surface of the isolation structure.
- 3.** The semiconductor device structure as claimed in claim 1, wherein the source/drain structure further has a second doped layer between the first doped layer and the undoped semiconductor layer, and a first dopant concentration of the first doped layer is greater than a second dopant concentration of the second doped layer.
- 4.** The semiconductor device structure as claimed in claim 3, wherein a first conductivity of the first doped layer is greater than a second conductivity of the second doped layer, and the second conductivity of the second doped layer is greater than a third conductivity of the undoped semiconductor layer.
- 5.** The semiconductor device structure as claimed in claim 3, wherein a first top surface of the second doped layer is between a second top surface of the first nanostructure and a second bottom surface of the second nanostructure.
- 6.** The semiconductor device structure as claimed in claim 5, wherein the first top surface of the second doped layer is a convex curved surface.
- 7.** The semiconductor device structure as claimed in claim 1, wherein the undoped semiconductor layer has a trapezoidal shape.
- 8.** The semiconductor device structure as claimed in claim 1, wherein the undoped semiconductor layer and the first doped layer have a substantially same width.
- 9.** A semiconductor device structure, comprising: a substrate having a base and a fin structure over the base, wherein the fin structure comprises a lower portion and a nanostructure over the lower portion; an isolation structure over the base and surrounding the lower portion; a gate stack wrapped around an upper portion of the fin structure; and a source/drain structure partially embedded in the isolation structure and the lower portion of the fin structure, wherein the source/drain structure has an undoped semiconductor layer and a first doped layer, the first doped layer is over the undoped semiconductor layer, a first bottom surface of the first doped layer is higher than a second bottom surface of the gate stack, the undoped semiconductor layer separates the first doped layer from the isolation structure and the lower portion, and the first doped layer is connected to the nanostructure.
- 10.** The semiconductor device structure as claimed in claim 9, wherein the source/drain structure further has a second doped layer, the second doped layer is between the first doped layer and the undoped semiconductor layer, a first dopant concentration of the first doped layer is greater than a second dopant concentration of the second doped layer, and a third bottom surface of the second doped layer is higher than the second bottom surface of the gate stack.
- 11.** The semiconductor device structure as claimed in claim 10, wherein the undoped semiconductor layer is thicker than the second doped layer, and the undoped semiconductor layer is thinner than the first doped layer.
- 12.** The semiconductor device structure as claimed in claim 9, wherein a third bottom surface of the undoped semiconductor layer is lower than the second bottom surface of the gate stack.

- 13.** The semiconductor device structure as claimed in claim 9, wherein the undoped semiconductor layer is partially embedded in the isolation structure and the lower portion of the fin structure.
- 14.** A semiconductor device structure, comprising: a substrate having a base and a fin structure over the base, wherein the fin structure comprises a lower portion, a first nanostructure, and a second nanostructure, and the first nanostructure is between the lower portion and the second nanostructure; an isolation structure over the base, wherein the isolation structure surrounds the lower portion; a gate stack over the fin structure and the isolation structure; and a source/drain structure partially embedded in the isolation structure and the lower portion of the fin structure, wherein the source/drain structure has an undoped semiconductor layer, a first doped layer, and a second doped layer, the first doped layer is between the undoped semiconductor layer and the second doped layer, the first doped layer is connected to the first nanostructure, and the undoped semiconductor layer is thicker than the first doped layer and thinner than the second doped layer.
- 15.** The semiconductor device structure as claimed in claim 14, wherein the second doped layer is connected to the second nanostructure.
- 16.** The semiconductor device structure as claimed in claim 14, wherein the undoped semiconductor layer has a convex curved top surface.
- 17.** The semiconductor device structure as claimed in claim 14, wherein the undoped semiconductor layer has a T-like shape.
- 18.** The semiconductor device structure as claimed in claim 14, wherein the undoped semiconductor layer is spaced apart from the first nanostructure.
- 19.** The semiconductor device structure as claimed in claim 18, wherein the second doped layer is spaced apart from the first nanostructure.
- 20.** The semiconductor device structure as claimed in claim 14, wherein a first dopant concentration of the first doped layer is less than a second dopant concentration of the second doped layer.
-