

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent
Kind Code
Date of Patent
Inventor(s)

12406941
B2
September 02, 2025
Chiang; Yi-Che et al.

Dielectric slots underneath conductive vias in interconnect structure of semiconductor package and method of forming the same

Abstract

A method of manufacturing a semiconductor package includes depositing a first dielectric layer over a carrier substrate. A first metallization pattern is formed over the first dielectric layer. The first metallization pattern has a first opening exposing the first dielectric layer. A second dielectric layer is deposited over the first metallization pattern, forming a dielectric slot through the first metallization pattern by filling the first opening. A second metallization pattern and a third dielectric layer are formed over the second dielectric layer. A through via is formed over the third dielectric layer, so that the dielectric slot is laterally under the through via.

Inventors: Chiang; Yi-Che (Hsinchu, TW), Chen; Chien-Hsun (Zhutian Township, TW), Hung; Tuan-Yu (Huatan Township, TW), Pan; Hsin-Yu (Taipei, TW), Hsieh; Wei-Kang (Tainan, TW), Chiang; Tsung-Hsien (Hsinchu, TW), Huang; Chao-Hsien (Kaohsiung, TW), Huang; Tzu-Sung (Tainan, TW), Tseng; Ming Hung (Toufen Township, TW), Chen; Wei-Chih (Taipei, TW), Wu; Ban-Li (Hsinchu, TW), Tsai; Hao-Yi (Hsinchu, TW), Hu; Yu-Hsiang (Hsinchu, TW), Liu; Chung-Shi (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Family ID: 86191009

Assignee: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Appl. No.: 17/752272

Filed: May 24, 2022

Prior Publication Data

Document Identifier
US 20230223357 A1

Publication Date
Jul. 13, 2023

Related U.S. Application Data

us-provisional-application US 63266523 20220107

Publication Classification

Int. Cl.: **H01L23/00** (20060101); **H01L21/48** (20060101); **H01L21/56** (20060101); **H01L21/683** (20060101); **H01L23/31** (20060101); **H01L23/538** (20060101); **H01L25/10** (20060101)

U.S. Cl.:

CPC **H01L23/562** (20130101); **H01L21/4853** (20130101); **H01L21/4857** (20130101); **H01L21/565** (20130101); **H01L21/568** (20130101); **H01L21/6835** (20130101); **H01L23/3128** (20130101); **H01L23/5383** (20130101); **H01L23/5386** (20130101); **H01L23/5389** (20130101); **H01L24/19** (20130101); **H01L24/20** (20130101); **H01L25/105** (20130101); H01L2221/68359 (20130101); H01L2224/214 (20130101); H01L2225/1035 (20130101); H01L2225/1058 (20130101); H01L2924/3511 (20130101); H01L2924/35121 (20130101)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9000584	12/2014	Lin et al.	N/A	N/A
9048222	12/2014	Hung et al.	N/A	N/A
9048233	12/2014	Wu et al.	N/A	N/A
9064879	12/2014	Hung et al.	N/A	N/A
9111949	12/2014	Yu et al.	N/A	N/A
9263511	12/2015	Yu et al.	N/A	N/A
9281254	12/2015	Yu et al.	N/A	N/A
9368460	12/2015	Yu et al.	N/A	N/A
9372206	12/2015	Wu et al.	N/A	N/A
9496189	12/2015	Yu et al.	N/A	N/A
9972581	12/2017	Yu et al.	N/A	N/A
10162139	12/2017	Wang et al.	N/A	N/A
2017/0228529	12/2016	Huang	N/A	H01L 23/3114
2018/0269139	12/2017	Chiang et al.	N/A	N/A
2020/0343193	12/2019	Hsieh	N/A	H01L 23/5384
2020/0365421	12/2019	Liu	N/A	H01L 21/561
2021/0151370	12/2020	Choi	N/A	H01L 21/486

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
201830639	12/2017	TW	N/A
201836109	12/2017	TW	N/A

Primary Examiner: Ojeh; Nduka E

Attorney, Agent or Firm: Slater Matsil, LLP

Background/Summary

PRIORITY CLAIM AND CROSS-REFERENCE (1) This application claims the benefit of U.S. Provisional Application No. 63/266,523, filed on Jan. 7, 2022, which application is hereby incorporated herein by reference.

BACKGROUND

(1) The semiconductor industry has experienced rapid growth due to ongoing improvements in the integration density of a variety of electronic components (e.g., transistors, diodes, resistors, capacitors, etc.). For the most part, improvement in integration density has resulted from iterative reduction of minimum feature size, which allows more components to be integrated into a given area. As the demand for shrinking electronic devices has grown, a need for smaller and more creative packaging techniques of semiconductor dies has emerged. An example of such packaging systems is Package-on-Package (PoP) technology. In a PoP device, a top semiconductor package is stacked on top of a bottom semiconductor package to provide a high level of integration and component density. PoP technology generally enables production of semiconductor devices with enhanced functionalities and small footprints on a printed circuit board (PCB).

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 illustrates a cross-sectional view of an integrated circuit die in accordance with some embodiments.

(3) FIGS. 2, 3A-3E, 4A-4E, 5A, 5B, 6A, 6B, 7A-7D, 8A, 8B, 9A, 9B, and 10 through 19 illustrate cross-sectional and top-down views of intermediate steps during a process for forming a package component in accordance with some embodiments.

(4) FIGS. 20, 21A, 21B, and 21C illustrate cross-sectional and top-down views of formation and implementation of device stacks in accordance with some embodiments.

(5) FIGS. 22A, 22B, 23A, 23B, 24, and 25 illustrate cross-sectional views of intermediate steps during a process for forming a package component in accordance with some embodiments.

(6) FIGS. 26A, 26B, and 26C illustrate cross-sectional and top-down views of formation and implementation of device stacks in accordance with some embodiments.

(7) FIGS. 27A, 27B, 28A, 28B, 29A, 29B, 30A, 30B, and 31 illustrate cross-sectional views of intermediate steps during a process for forming a package component in accordance with some embodiments.

(8) FIGS. 32A and 32B illustrate cross-sectional views of formation and implementation of device stacks in accordance with some embodiments.

(9) FIGS. 33 through 37A-37C illustrate cross-sectional and top-down views of formation and implementation of device stacks in accordance with some embodiments.

DETAILED DESCRIPTION

(10) The following disclosure provides many different embodiments, or examples, for implementing different features of the invention. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(11) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(12) In accordance with some embodiments, a semiconductor package includes a back-side redistribution structure having multiple layers of metallization patterns. The back-side redistribution structure having multiple layers of metallization patterns may be advantageous for increasing routing ability, such as for routing between system-on-chips (SoCs) and DRAM packages attached to the back-side redistribution structure.

(13) Some embodiments of the current disclosure decrease stress between layers of the back-side redistribution structure at positions underneath through vias. Embodiments may address stress arising from mismatches in respective coefficients of thermal expansion of through vias and adjacent encapsulant material. The embodiments may reduce stress under respective bases of the through vias in the back-side redistribution structure occurring during high temperature processes such as curing of encapsulant material or mounting and reflowing of solder ball connectors that lead to, e.g., greater expansion of the encapsulant material relative to expansion of the through vias. The embodiments decrease stress and disadvantageous delamination between metallization patterns and dielectric layers of the back-side redistribution structure. Including dielectric slots in a metallization pattern below respective footprints of the through vias can decrease the stress producing the delamination. The delamination may also be reduced by adjusting relative thicknesses of dielectric layers of the back-side redistribution structure or including an adhesion layer over a metallization pattern.

(14) FIG. 1 illustrates a cross-sectional view of an integrated circuit die 50 in accordance with some embodiments. The integrated circuit die 50 will be packaged in subsequent processing to form an integrated circuit package. The integrated circuit die 50 may be a logic die (e.g., central processing unit (CPU), graphics processing unit (GPU), system-on-a-chip (SoC), application processor (AP), microcontroller, etc.), a memory die (e.g., dynamic random access memory (DRAM) die, static random access memory (SRAM) die, etc.), a power management die (e.g., power management integrated circuit (PMIC) die), a radio frequency (RF) die, a sensor die, a micro-electro-mechanical-system (MEMS) die, a signal processing die (e.g., digital signal processing (DSP) die), a front-end die (e.g., analog front-end (AFE) dies), the like, or combinations thereof.

(15) The integrated circuit die 50 may be formed in a wafer, which may include different device regions that are singulated in subsequent steps to form a plurality of integrated circuit dies. The integrated circuit die 50 may be processed according to applicable manufacturing processes to form

integrated circuits. For example, the integrated circuit die **50** includes a semiconductor substrate **52**, such as silicon, doped or undoped, or an active layer of a semiconductor-on-insulator (SOI) substrate. The semiconductor substrate **52** may include other semiconductor materials, such as germanium; a compound semiconductor including silicon carbide, gallium arsenic, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor including SiGe, GaAsP, AlInAs, AlGaAs, GaInAs, GaInP, and/or GaInAsP; or combinations thereof. Other substrates, such as multi-layered or gradient substrates, may also be used. The semiconductor substrate **52** has an active surface (e.g., the surface facing upwards in FIG. **1**), sometimes called a front-side, and an inactive surface (e.g., the surface facing downwards in FIG. **1**), sometimes called a back-side.

(16) Devices (represented by a transistor) **54** may be formed at the front surface of the semiconductor substrate **52**. The devices **54** may be active devices (e.g., transistors, diodes, etc.), capacitors, resistors, etc. An inter-layer dielectric (ILD) **56** is over the front surface of the semiconductor substrate **52**. The ILD **56** surrounds and may cover the devices **54**. The ILD **56** may include one or more dielectric layers formed of materials such as Phospho-Silicate Glass (PSG), Boro-Silicate Glass (BSG), Boron-Doped Phospho-Silicate Glass (BPSG), undoped Silicate Glass (USG), or the like.

(17) Conductive plugs **58** extend through the ILD **56** to electrically and physically couple the devices **54**. For example, when the devices **54** are transistors, the conductive plugs **58** may couple the gates and source/drain regions of the transistors. The conductive plugs **58** may be formed of tungsten, cobalt, nickel, copper, silver, gold, aluminum, the like, or combinations thereof. An interconnect structure **60** is over the ILD **56** and conductive plugs **58**. The interconnect structure **60** interconnects the devices **54** to form an integrated circuit. The interconnect structure **60** may be formed by, for example, metallization patterns in dielectric layers on the ILD **56**. The metallization patterns include metal lines and vias formed in one or more low-k dielectric layers. The metallization patterns of the interconnect structure **60** are electrically coupled to the devices **54** by the conductive plugs **58**.

(18) The integrated circuit die **50** further includes pads **62**, such as aluminum pads, to which external connections are made. The pads **62** are on the active side of the integrated circuit die **50**, such as in and/or on the interconnect structure **60**. One or more passivation films **64** are on the integrated circuit die **50**, such as on portions of the interconnect structure **60** and pads **62**. Openings extend through the passivation films **64** to the pads **62**. Die connectors **66**, such as conductive pillars (for example, formed of a metal such as copper), extend through the openings in the passivation films **64** and are physically and electrically coupled to respective ones of the pads **62**. The die connectors **66** may be formed by, for example, plating, or the like. The die connectors **66** electrically couple the respective integrated circuits of the integrated circuit die **50**.

(19) Optionally, solder regions (e.g., solder balls or solder bumps) may be disposed on the pads **62**. The solder balls may be used to perform chip probe (CP) testing on the integrated circuit die **50**. CP testing may be performed on the integrated circuit die **50** to ascertain whether the integrated circuit die **50** is a known good die (KGD). Thus, only integrated circuit dies **50**, which are KGDs, undergo subsequent processing and are packaged, and dies, which fail the CP testing, are not packaged. After testing, the solder regions may be removed in subsequent processing steps.

(20) A dielectric layer **68** may (or may not) be on the active side of the integrated circuit die **50**, such as on the passivation films **64** and the die connectors **66**. The dielectric layer **68** laterally encapsulates the die connectors **66**, and the dielectric layer **68** is laterally coterminous with the integrated circuit die **50**. Initially, the dielectric layer **68** may bury the die connectors **66**, such that the topmost surface of the dielectric layer **68** is above the topmost surfaces of the die connectors **66**. In some embodiments where solder regions are disposed on the die connectors **66**, the dielectric layer **68** may bury the solder regions as well. Alternatively, the solder regions may be removed prior to forming the dielectric layer **68**.

(21) The dielectric layer **68** may be a polymer such as PBO, polyimide, BCB, or the like; a nitride such as silicon nitride or the like; an oxide such as silicon oxide, PSG, BSG, BPSG, or the like; the like, or a combination thereof. The dielectric layer **68** may be formed, for example, by spin coating, lamination, chemical vapor deposition (CVD), or the like. In some embodiments, the die connectors **66** are exposed through the dielectric layer **68** during formation of the integrated circuit die **50**. In some embodiments, the die connectors **66** remain buried and are exposed during a subsequent process for packaging the integrated circuit die **50**. Exposing the die connectors **66** may remove any solder regions that may be present on the die connectors **66**.

(22) In some embodiments, the integrated circuit die **50** is a stacked device that includes multiple semiconductor substrates **52**. For example, the integrated circuit die **50** may be a memory device such as a hybrid memory cube (HMC) module, a high bandwidth memory (HBM) module, or the like that includes multiple memory dies. In such embodiments, the integrated circuit die **50** includes multiple semiconductor substrates **52** interconnected by through-substrate vias (TSVs). Each of the semiconductor substrates **52** may (or may not) have an interconnect structure **60**.

(23) FIGS. **2** through **19** illustrate cross-sectional and plan views of intermediate steps during a process for forming a first package component **100**, in accordance with some embodiments. A first package region **100A** and a second package region **100B** are illustrated, and one or more of the integrated circuit dies **50** are packaged to form an integrated circuit package in each of the package regions **100A** and **100B**. The integrated circuit packages may also be referred to as integrated fan-out (InFO) packages.

(24) In FIG. **2**, a carrier substrate **102** is provided, and a release layer **104** is formed on the carrier substrate **102**. The carrier substrate **102** may be a glass carrier substrate, a ceramic carrier substrate, or the like. The carrier substrate **102** may be a wafer, such that multiple packages can be formed on the carrier substrate **102** simultaneously.

(25) The release layer **104** may be formed of a polymer-based material, which may be removed along with the carrier substrate **102** from the overlying structures that will be formed in subsequent steps. In some embodiments, the release layer **104** is an epoxy-based thermal-release material, which loses its adhesive property when heated, such as a light-to-heat-conversion (LTHC) release coating. In other embodiments, the release layer **104** may be an ultra-violet (UV) glue, which loses its adhesive property when exposed to UV lights. The release layer **104** may be dispensed as a liquid and cured, may be a laminate film laminated onto the carrier substrate **102**, or may be the like. The top surface of the release layer **104** may be leveled and may have a high degree of planarity.

(26) In FIGS. **3A** through **6B**, a back-side redistribution structure **106** is formed on the release layer **104**. As discussed in greater detail below, the back-side redistribution structure **106** is formed and through vias are formed over the back-side redistribution structure. The back-side redistribution structure **106** may include one or more dielectric layers and metallization patterns (sometimes referred to as redistribution layers or redistribution lines) between adjacent ones of the dielectric layers. The back-side redistribution structure **106** includes dielectric slots in the metallization pattern below the footprints of one or more of the through vias. The dielectric slots may reduce the stress between various layers, such as between the layers of the metallization patterns and the dielectric layers of the back-side redistribution structure, thereby reducing delamination issues.

(27) FIG. **3A** illustrates the formation of the dielectric layer **108** and a metallization pattern **110** of the back-side redistribution structure **106**. The metallization pattern **110** may include conductive redistribution lines used for routing and/or dummy patterns. As illustrated in FIG. **3A**, the metallization pattern **110** is patterned to include regions **109** (which represents the region below subsequently formed through vias) that are free of conductive patterns (e.g., free of the conductive redistribution lines and/or the dummy patterns). FIG. **3B** illustrates a detailed cross-sectional view of region **101** as illustrated in FIG. **3A**. As discussed in greater detail below, a through via will be formed over the region **109** of the redistribution structure **106**, and having region **109** free of

conductive material below the through via may reduce stress. FIGS. 3C-3E illustrate plan views of embodiments of the structure at the level of the metallization pattern **110** in a region surrounding the region **109**. Subsequent figures following from FIGS. 3C-3E will illustrate plan views at the same level.

(28) As shown in FIG. 3A, the dielectric layer **108** may be formed over the release layer **104**. The bottom surface of the dielectric layer **108** may be in contact with the top surface of the release layer **104**. In some embodiments, the dielectric layer **108** is formed of a polymer, such as polybenzoxazole (PBO), polyimide, benzocyclobutene (BCB), or the like. In other embodiments, the dielectric layer **108** is formed of a nitride such as silicon nitride; an oxide such as silicon oxide, phosphosilicate glass (PSG), borosilicate glass (BSG), boron-doped phosphosilicate glass (BPSG), or the like; or the like. The dielectric layer **108** may be formed by any acceptable deposition process, such as spin coating, CVD, laminating, the like, or a combination thereof.

(29) The metallization pattern **110** may be formed on the dielectric layer **108**. In some embodiments as illustrated in FIGS. 3C and 3D, the metallization pattern **110** includes a dummy pattern, such as a metal grid or mesh. For example, FIGS. 3C and 3D illustrate embodiments in which the metallization pattern **110** includes a dummy pattern having a shape similar to a first plurality of strips having lengthwise directions in the X-direction intersecting a second plurality of strips having lengthwise directions in the Y-direction, which may be (or may not be) perpendicular to the X-direction. The dummy pattern may be electrically isolated from active conductive lines and vias of the metallization pattern **110**. Including the dummy pattern may be advantageous by increasing the density of metal in the back-side redistribution structure **106** and thereby reducing subsequent package warpage. Although the dummy pattern is illustrated as a continuous metal grid in FIGS. 3C and 3D, in some embodiments as the dummy pattern may be separated into multiple electrically isolated areas.

(30) In some embodiments as illustrated in FIG. 3E, the region **109** is positioned amongst a pattern of active conductive lines of the metallization pattern **110**, and the active conductive lines are arranged in a manner such that a region **109** is free of the metallization pattern **110**.

(31) As an example to form metallization pattern **110**, a seed layer is formed over the dielectric layer **108**. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, physical vapor deposition (PVD) or the like. A photoresist (not shown) is then formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to the metallization pattern **110**. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, like copper, titanium, tungsten, aluminum, or the like. Then, the photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching. The remaining portions of the seed layer and conductive material form the metallization pattern **110**.

(32) As illustrated by FIGS. 3B-3D, regions **109** expose the dielectric layer **108** through the metallization pattern **110**. FIG. 3C illustrates a metallization pattern **110** having a dummy pattern (e.g., a metal grid pattern), wherein the dummy pattern omits conductive material in the region **109**. The illustrated embodiment in FIG. 3C illustrates region **109** having a round shape in which the region **109** does not intersect smaller openings through the dummy pattern of the metallization pattern **110**. FIG. 3D illustrates the region **109** with a round shape that intersects or overlaps

smaller openings in the dummy pattern of the metallization pattern **110**. The regions **109** are subsequently filled with dielectric material to form dielectric slots **111** (see below, FIGS. **4A-4D**) underneath subsequently formed through vias **116**. This may be advantageous by reducing delamination between the metallization pattern **110** and the subsequently formed dielectric layer **112**. In some embodiments, the regions **109** have round shapes in a top view, as illustrated by FIGS. **3C** and **3D**. In some embodiments, the regions **109** have other shapes such as square shapes, hexagonal shapes, or octagonal shapes. However, any suitable shape may be used for the region **109**.

(33) In FIGS. **4A-4E**, the dielectric layer **112** is formed on the metallization pattern **110** and the dielectric layer **108**. In some embodiments, the dielectric layer **112** is formed of a polymer, which may be a photo-sensitive material such as PBO, polyimide, BCB, or the like, that may be patterned using a lithography mask. In other embodiments, the dielectric layer **112** is formed of a nitride such as silicon nitride; an oxide such as silicon oxide, PSG, BSG, BPSG; or the like. The dielectric layer **112** may be formed by spin coating, lamination, CVD, the like, or a combination thereof.

(34) As illustrated by FIGS. **4B-4E**, the dielectric layer **112** fills the region **109**, forming dielectric slots **111** in the metallization pattern **110**. Other openings through the metallization pattern **110** (e.g., square or rectangular openings in the dummy pattern, spaces between redistribution lines, etc.) are also filled with dielectric material of the dielectric layer **112**. In some embodiments, the respective surface areas of the dielectric slots are larger than the respective surface areas of square or rectangular regions of the dummy pattern. The dielectric slots **111** are positioned under subsequently formed through vias **116**, which may reduce delamination between the metallization pattern **110** and the dielectric layer **112**. In some embodiments, the dielectric slots **111** are surrounded by conductive material of the metallization pattern **110** in a top view. In some embodiments, the dielectric slots **111** have respective first widths $W_{sub.1}$ in a range of 55 μm to 65 μm , which is advantageous for reducing delamination between the metallization pattern **110** and the dielectric layer **112**. Forming the dielectric slots **111** to widths less than 55 μm may not sufficiently reduce stress from mismatched thermal expansions of subsequently formed through vias **116** and encapsulant **120** (see below, FIG. **9A**), leading to disadvantageous delamination between the metallization pattern **110** and the dielectric layer **112**. Forming the dielectric slots **111** to widths greater than 65 μm may increase resistance in the metallization pattern **110**, reducing device performance. As illustrated in FIG. **4E**, in some embodiments the respective first widths $W_{sub.1}$ are larger than first spaces $S_{sub.1}$ between adjacent conductive lines of the metallization pattern **110**.

(35) In some embodiments, the dielectric slots **111** have round shapes in a plan view, as illustrated by FIGS. **4C-4E**. In some embodiments, the dielectric slots **111** have other shapes such as square shapes, hexagonal shapes, or octagonal shapes. However, any suitable shape may be used for the dielectric slots **111**.

(36) Forming the dielectric slots **111** to reduce delamination between the metallization pattern **110** and the dielectric layer **112** may provide advantages. Forming the dielectric slots **111** may reduce the cost of the structure, as the dielectric layers of the back-side redistribution structure **106** (e.g., the dielectric layer **112**) may not need to be thickened. As the dielectric layers of the back-side redistribution structure **106** are not thickened, the wafer-per-hour (WPH) rate of mass production may be increased. Reducing delamination between the metallization pattern **110** and the dielectric layer **112** by forming the dielectric slots **111** may lead to lower process warpage of the structure, giving better process yield loss control as well as better reliability performance and wider reliability window. In some embodiments, forming the dielectric slots **111** under the footprints of subsequently formed through vias **116** reduces stress between the metallization pattern **110** and the dielectric layer **112** by 18% to 30%.

(37) Further referring to FIG. **4A**, the dielectric layer **112** is then patterned to form openings exposing portions of the metallization pattern **110**. The patterning may be formed by an acceptable

process, such as by exposing the dielectric layer **112** to light when the dielectric layer **112** is a photo-sensitive material or by etching using, for example, an anisotropic etch. If the dielectric layer **112** is a photo-sensitive material, the dielectric layer **112** can be developed after the exposure. (38) In FIGS. 5A-5B, the metallization pattern **113** is formed on the dielectric layer **112**. The metallization pattern **113** includes portions on and extending along the major surface of the dielectric layer **112**. The metallization pattern **113** further includes portions extending through the dielectric layer **112** to physically and electrically couple to the metallization pattern **110**. The metallization pattern **113** may be formed in a similar manner and of a similar material as the metallization pattern **110**. In some embodiments, the metallization pattern **113** has a different size than the metallization pattern **110**. For example, the conductive lines and/or vias of the metallization pattern **113** may be wider or thicker than the conductive lines and/or vias of the metallization pattern **110**. Further, the metallization pattern **113** may be formed to a greater pitch than the metallization pattern **110**.

(39) In FIGS. 6A-6B, the dielectric layer **114** is deposited on the metallization pattern **113** and the dielectric layer **112**. The dielectric layer **114** may be formed in a manner similar to the dielectric layer **112**, and may be formed of a similar material as the dielectric layer **112**. The dielectric layer **114** is then patterned to form openings **115** exposing portions of the metallization pattern **113**. The patterning may be formed by an acceptable process, such as by exposing the dielectric layer **114** to light when the dielectric layer **114** is a photo-sensitive material or by etching using, for example, an anisotropic etch. If the dielectric layer **114** is a photo-sensitive material, the dielectric layer **114** can be developed after the exposure. The openings **115** are subsequently filled with conductive material to form conductive vias **117** coupling the metallization pattern **113** to subsequently formed through vias **116** (see below, FIGS. 7A-7B).

(40) FIG. 6A illustrates a back-side redistribution structure **106** having two metallization patterns **110** and **113** for illustrative purposes. In some embodiments, the back-side redistribution structure **106** may include any number of dielectric layers and metallization patterns. If more dielectric layers and metallization patterns are to be formed, steps and processes discussed above may be repeated. The metallization patterns may include one or more conductive elements. The conductive elements may be formed during the formation of the metallization pattern by forming the seed layer and conductive material of the metallization pattern over a surface of the underlying dielectric layer and in the opening of the underlying dielectric layer, thereby interconnecting and electrically coupling various conductive lines.

(41) In FIGS. 7A-7B, through vias **116** are formed in the openings **115** and extending away from the topmost dielectric layer of the back-side redistribution structure **106** (e.g., the dielectric layer **112**). The through vias **116** include vias **117** that are below upper surfaces of the dielectric layer **114**. The vias **117** and through vias **116** are formed overlying the dielectric slots **111**. As an example to form the through vias **116**, a seed layer (not shown) is formed over the back-side redistribution structure **106**, e.g., on the dielectric layer **112** and portions of the metallization pattern **110** exposed by the openings **115**. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In a particular embodiment, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. A photoresist is formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to conductive vias. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, like copper, titanium, tungsten, aluminum, or the like. The photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or

stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching. The remaining portions of the seed layer and conductive material form the through vias **116**, with portions below upper surfaces of the dielectric layer **114** being vias **117** extending through the dielectric layer **114** to the uppermost metallization layer, such as metallization pattern **113**.

(42) In some embodiments, the through vias **116** have widths in a range of 150 μm to 200 μm , and adjacent through vias **116** are separated from each other by spaces in a range of 120 μm to 150 μm . The widths of the through vias **116** may be greater than the respective first widths $W_{\text{sub.1}}$ of the dielectric slots **111** underneath the through vias **116**. For example, the respective first widths $W_{\text{sub.1}}$ may be 33% to 43% of the widths of the through vias **116**. In some embodiments, the vias **117** are laterally separated from conductive vias of lower metallization patterns. For example, FIG. 7A illustrates that the via **117** the through via **116** is laterally separated from the via of the metallization pattern **113** that extends to physically and electrically contact the metallization pattern **110** by a distance $D_{\text{sub.1}}$, such as in a range of 17 μm to 18 μm .

(43) The vias **117** are formed to have respective second widths $W_{\text{sub.2}}$ smaller than respective first widths $W_{\text{sub.1}}$ of the dielectric slots **111** beneath the vias **117**. This is advantageous by reducing stress from mismatched thermal expansions of the through vias **116** and subsequently formed encapsulant **120** (see below, FIG. 9A), which may prevent or reduce delamination between the metallization pattern **110** and the dielectric layer **112**. In some embodiments, the second widths $W_{\text{sub.2}}$ are in a range of 40 μm to 50 μm .

(44) In some embodiments, a portion **110'** of the metallization pattern **110** (e.g., a portion of a dummy pattern, a portion of a redistribution line, or the like) extends under the footprint of the via **117**. For example, FIG. 7C illustrates a side view showing portion **110'** of the metallization pattern **110** within a footprint of a via **117** at the level of the metallization pattern **110**, and FIG. 7D illustrates a plan view showing the portion **110'** of the metallization pattern **110** within the footprint of the via **117** at the level of the metallization pattern **110**, in accordance with some embodiments. A total amount of an upper surface area of the portion **110'**, which may include conductive material of redistribution lines, dummy patterns, or the like, has an upper surface area less than 20% of a surface area of the via **117**. This is advantageous for preventing or reducing delamination between the metallization pattern **110** and the dielectric layer **112**. A portion **110'** of conductive material with an upper surface area 65% or greater of a surface area of the via **117** being present under the respective footprint of the via **117** at the level of the metallization pattern **110** may be disadvantageous by leading to delamination between the metallization pattern **110** and the dielectric layer **112**. In some embodiments, a total upper surface area of the portion **110'** is less than 1500 μm^2 .

(45) In FIGS. 8A-8B, integrated circuit dies **50** (e.g., a first integrated circuit die **50A** and a second integrated circuit die **50B**) are adhered to the dielectric layer **112** by an adhesive **118**. A desired type and quantity of integrated circuit dies **50** are adhered in each of the package regions **100A** and **100B**. In the embodiment shown, multiple integrated circuit dies **50** are adhered adjacent one another, including the first integrated circuit die **50A** and the second integrated circuit die **50B** in each of the first package region **100A** and the second package region **100B**. The first integrated circuit die **50A** may be a logic device, such as a central processing unit (CPU), a graphics processing unit (GPU), a system-on-a-chip (SoC), a microcontroller, or the like. The second integrated circuit die **50B** may be a memory device, such as a dynamic random access memory (DRAM) die, a static random access memory (SRAM) die, a hybrid memory cube (HMC) module, a high bandwidth memory (HBM) module, or the like. In some embodiments, the integrated circuit dies **50A** and **50B** may be the same type of dies, such as SoC dies. The first integrated circuit die **50A** and second integrated circuit die **50B** may be formed in processes of a same technology node, or may be formed in processes of different technology nodes. For example, the first integrated

circuit die **50A** may be of a more advanced process node than the second integrated circuit die **50B**. The integrated circuit dies **50A** and **50B** may have different sizes (e.g., different heights and/or surface areas), or may have the same size (e.g., same heights and/or surface areas). The space available for the through vias **116** in the first package region **100A** and the second package region **100B** may be limited, particularly when the integrated circuit dies **50** include devices with a large footprint, such as SoCs. Use of the back-side redistribution structure **106** allows for an improved interconnect arrangement when the first package region **100A** and the second package region **100B** have limited space available for the through vias **116**.

(46) The adhesive **118** is on back-sides of the integrated circuit dies **50** and adheres the integrated circuit dies **50** to the back-side redistribution structure **106**, such as to the dielectric layer **112**. The adhesive **118** may be any suitable adhesive, epoxy, die attach film (DAF), or the like. The adhesive **118** may be applied to back-sides of the integrated circuit dies **50**, may be applied over the surface of the carrier substrate **102** if no back-side redistribution structure **106** is utilized, or may be applied to an upper surface of the back-side redistribution structure **106** if applicable. For example, the adhesive **118** may be applied to the back-sides of the integrated circuit dies **50** before singulating to separate the integrated circuit dies **50**.

(47) In FIGS. **9A-9B**, an encapsulant **120** is formed on and around the various components. After formation, the encapsulant **120** encapsulates the through vias **116** and integrated circuit dies **50**. The encapsulant **120** may be a molding compound, epoxy, or the like. The encapsulant **120** may be applied by compression molding, transfer molding, or the like, and may be formed over the carrier substrate **102** such that the through vias **116** and/or the integrated circuit dies **50** are buried or covered. The encapsulant **120** is further formed in gap regions between the integrated circuit dies **50**. The encapsulant **120** may be applied in liquid or semi-liquid form and then subsequently cured.

(48) The curing of the encapsulant **120** may be a high temperature process and may lead to greater expansion of the encapsulant **120** relative to expansion of the through vias **116**, producing increased stress under respective bases of the through vias **116** in the back-side redistribution structure **106**. The inclusion of dielectric slots **111** in the metallization pattern **110** under the respective footprints of the through vias **116** such as described herein may prevent or reduce delamination between, e.g., the metallization pattern **110** and the dielectric layer **112**.

(49) In FIG. **10**, a planarization process is performed on the encapsulant **120** to expose the through vias **116** and the die connectors **66**. The planarization process may also remove material of the through vias **116**, dielectric layer **68**, and/or die connectors **66** until the die connectors **66** and through vias **116** are exposed. Top surfaces of the through vias **116**, die connectors **66**, dielectric layer **68**, and encapsulant **120** are substantially coplanar after the planarization process within process variations. The planarization process may be, for example, a chemical-mechanical polish (CMP), a grinding process, or the like. In some embodiments, the planarization may be omitted, for example, if the through vias **116** and/or die connectors **66** are already exposed.

(50) In FIGS. **11** through **14**, a front-side redistribution structure **122** is formed over the encapsulant **120**, through vias **116**, and integrated circuit dies **50**. The front-side redistribution structure **122** may include one or more dielectric layers and metallization patterns (sometimes referred to as redistribution layers or redistribution lines) between adjacent ones of the dielectric layers.

(51) In FIG. **11**, the dielectric layer **124** is deposited on the encapsulant **120**, through vias **116**, and die connectors **66**. In some embodiments, the dielectric layer **124** is formed of a photo-sensitive material such as PBO, polyimide, BCB, or the like, which may be patterned using a lithography mask. The dielectric layer **124** may be formed by spin coating, lamination, CVD, the like, or a combination thereof. The dielectric layer **124** is then patterned. The patterning forms openings exposing portions of the through vias **116** and the die connectors **66**. The patterning may be by an acceptable process, such as by exposing and developing the dielectric layer **124** to light when the dielectric layer **124** is a photo-sensitive material or by etching using, for example, an anisotropic

etch.

(52) The metallization pattern **126** is then formed. The metallization pattern **126** includes conductive elements extending along the major surface of the dielectric layer **124** and extending through the dielectric layer **124** to physically and electrically couple to the through vias **116** and the integrated circuit dies **50**. As an example to form the metallization pattern **126**, a seed layer is formed over the dielectric layer **124** and in the openings extending through the dielectric layer **124**. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. A photoresist is then formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to the metallization pattern **126**. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is then formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, like copper, titanium, tungsten, aluminum, or the like. The combination of the conductive material and underlying portions of the seed layer form the metallization pattern **126**. The photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching.

(53) In FIG. **12**, the dielectric layer **128** is deposited on the metallization pattern **126** and the dielectric layer **124**. The dielectric layer **128** may be formed in a manner similar to the dielectric layer **124**, and may be formed of a similar material as the dielectric layer **124**.

(54) The metallization pattern **130** is then formed. The metallization pattern **130** includes portions on and extending along the major surface of the dielectric layer **128**. The metallization pattern **130** further includes portions extending through the dielectric layer **128** to physically and electrically couple the metallization pattern **126**. The metallization pattern **130** may be formed in a similar manner and of a similar material as the metallization pattern **126**. In some embodiments, the metallization pattern **130** has a different size than the metallization pattern **126**. For example, the conductive lines and/or vias of the metallization pattern **130** may be wider or thicker than the conductive lines and/or vias of the metallization pattern **126**. Further, the metallization pattern **130** may be formed to a greater pitch than the metallization pattern **126**.

(55) In FIG. **13**, the dielectric layer **132** is deposited on the metallization pattern **130** and the dielectric layer **128**. The dielectric layer **132** may be formed in a manner similar to the dielectric layer **124**, and may be formed of a similar material as the dielectric layer **124**.

(56) The metallization pattern **134** is then formed. The metallization pattern **134** includes portions on and extending along the major surface of the dielectric layer **132**. The metallization pattern **134** further includes portions extending through the dielectric layer **132** to physically and electrically couple the metallization pattern **130**. The metallization pattern **134** may be formed in a similar manner and of a similar material as the metallization pattern **126**. The metallization pattern **134** is the topmost metallization pattern of the front-side redistribution structure **122**. As such, all of the intermediate metallization patterns of the front-side redistribution structure **122** (e.g., the metallization patterns **126** and **130**) are disposed between the metallization pattern **134** and the integrated circuit dies **50**. In some embodiments, the metallization pattern **134** has a different size than the metallization patterns **126** and **130**. For example, the conductive lines and/or vias of the metallization pattern **134** may be wider or thicker than the conductive lines and/or vias of the metallization patterns **126** and **130**. Further, the metallization pattern **134** may be formed to a greater pitch than the metallization pattern **130**.

(57) In FIG. 14, the dielectric layer **136** is deposited on the metallization pattern **134** and the dielectric layer **132**. The dielectric layer **136** may be formed in a manner similar to the dielectric layer **124**, and may be formed of the same material as the dielectric layer **124**. The dielectric layer **136** is the topmost dielectric layer of the front-side redistribution structure **122**. As such, all of the metallization patterns of the front-side redistribution structure **122** (e.g., the metallization patterns **126**, **130**, and **134**) are disposed between the dielectric layer **136** and the integrated circuit dies **50**. Further, all of the intermediate dielectric layers of the front-side redistribution structure **122** (e.g., the dielectric layers **124**, **128**, **132**) are disposed between the dielectric layer **136** and the integrated circuit dies **50**.

(58) The front-side redistribution structure **122** is shown as an example having three layers of metallization patterns. More or fewer dielectric layers and metallization patterns may be formed in the front-side redistribution structure **122**. If fewer dielectric layers and metallization patterns are to be formed, steps and process discussed above may be omitted. If more dielectric layers and metallization patterns are to be formed (e.g., four dielectric layers and five metallization patterns), steps and processes discussed above may be repeated.

(59) In FIG. 15, UBMs **138** are formed for external connection to the front-side redistribution structure **122**. In some embodiments, the UBMs **138** have respective concave upper surfaces with upper portions on and extending along the major surface of the dielectric layer **136**, and have lower portions extending through the dielectric layer **136** to physically and electrically couple the metallization pattern **134**. In some embodiments, the UBMs **138** have flat or convex upper surfaces on and extending along the major surface of the dielectric layer **136**. As a result, the UBMs **138** are electrically coupled to the through vias **116** and the integrated circuit dies **50**. The UBMs **138** may be formed of the same material as the metallization pattern **126**. In some embodiments, the UBMs **138** have a different size than the metallization patterns **126**, **130**, and **134**.

(60) In FIG. 16, conductive connectors **150** are formed on the UBMs **138**. The conductive connectors **150** may be ball grid array (BGA) connectors, solder balls, metal pillars, controlled collapse chip connection (C4) bumps, micro bumps, electroless nickel-electroless palladium-immersion gold technique (ENEPIG) formed bumps, or the like. The conductive connectors **150** may include a conductive material such as solder, copper, aluminum, gold, nickel, silver, palladium, tin, the like, or a combination thereof. In some embodiments, the conductive connectors **150** are formed by initially forming a layer of solder through evaporation, electroplating, printing, solder transfer, ball placement, or the like. Once a layer of solder has been formed on the structure, a reflow may be performed in order to shape the material into the desired bump shapes. In another embodiment, the conductive connectors **150** comprise metal pillars (such as a copper pillar) formed by sputtering, printing, electro plating, electroless plating, CVD, or the like. The metal pillars may be solder free and have substantially vertical sidewalls. In some embodiments, a metal cap layer is formed on the top of the metal pillars. The metal cap layer may include nickel, tin, tin-lead, gold, silver, palladium, indium, nickel-palladium-gold, nickel-gold, the like, or a combination thereof and may be formed by a plating process.

(61) In FIG. 17, a carrier substrate de-bonding is performed to detach (or “de-bond”) the carrier substrate **102** from the back-side redistribution structure **106**, e.g., the dielectric layer **108**. In accordance with some embodiments, the de-bonding includes projecting a light such as a laser light or an UV light on the release layer **104** so that the release layer **104** decomposes under the heat of the light and the carrier substrate **102** can be removed. The structure is then flipped over and placed on a tape (not shown).

(62) In some embodiments, a back-side enhancement layer **140** is formed over the back-side redistribution structure **106** to reduce or prevent package warping. The back-side enhancement layer **140** may be a polymer such as PBO, polyimide, BCB, or the like; a nitride such as silicon nitride or the like; an oxide such as silicon oxide, PSG, BSG, BPSG, or the like; the like, or a combination thereof. The back-side enhancement layer **140** may be formed, for example, by spin

coating, lamination, chemical vapor deposition (CVD), or the like.

(63) In FIG. 19, conductive connectors **152** are formed extending through the back-side enhancement layer **140** (if present) and the dielectric layer **108** to contact the metallization pattern **110**. Openings are formed through the back-side enhancement layer **140** (if present) and the dielectric layer **108** to expose portions of the metallization pattern **110**. The openings may be formed, for example, using laser drilling, etching, or the like. Exposed portions of the seed layer (if present, see above, FIG. 3A) may be removed during the formation of the openings. Following the formation of the openings, a surface clean process may be used to remove residue and byproducts resulting from the laser drilling, etching, or the like. A surface cleaning chemical, mixture, or solution may be used such as HF, HCl, H.sub.2SO.sub.4:H.sub.2O (Sulfuric acid-hydrogen Peroxide Mixture (SPM)), NH.sub.4OH:H.sub.2O.sub.2:H.sub.2O (Ammonia hydroxide-hydrogen Peroxide-water Mixture (APM)), HCl:H.sub.2O.sub.2:H.sub.2O (Hydrochloric acid-hydrogen Peroxide-water Mixture (HPM)), the like, or combinations thereof, respectively.

(64) The conductive connectors **152** are formed in the openings. In some embodiments, the conductive connectors **152** comprise flux and are formed in a flux dipping process. In some embodiments, the conductive connectors **152** comprise a conductive paste such as solder paste, silver paste, or the like, and are dispensed in a printing process. In some embodiments, the conductive connectors **152** are formed in a manner similar to the conductive connectors **150**, and may be formed of a similar material as the conductive connectors **150**.

(65) In some embodiments, the conductive connectors **152** extend above the exposed surface of the back-side redistribution structure **106** (including the back-side enhancement layer **140**, if present). In some embodiments, top surfaces of the conductive connectors **152** are formed to be below the exposed surface of the back-side redistribution structure **106** (including the back-side enhancement layer, if present). Furthermore, a laser marking step may be performed on the exposed surface of the back-side redistribution structure **106** (e.g., the back-side enhancement layer **140** if present) to form identification marks (not shown).

(66) FIGS. 20 and 21 illustrate formation and implementation of device stacks, in accordance with some embodiments. The device stacks are formed from the integrated circuit packages formed in the first package component **100**. The device stacks may also be referred to as package-on-package (PoP) structures.

(67) In FIG. 20, second package components **200** are coupled to the first package component **100**. One of the second package components **200** is coupled in each of the package regions **100A** and **100B** to form an integrated circuit device stack in each region of the first package component **100**.

(68) The second package components **200** include, for example, a substrate **202** and one or more stacked dies **210** (e.g., **210A** and **210B**) coupled to the substrate **202**. Although one set of stacked dies **210** (**210A** and **210B**) is illustrated, in other embodiments, a plurality of stacked dies **210** (each having one or more stacked dies) may be disposed side-by-side coupled to a same surface of the substrate **202**. The substrate **202** may be made of a semiconductor material such as silicon, germanium, diamond, or the like. In some embodiments, compound materials such as silicon germanium, silicon carbide, gallium arsenic, indium arsenide, indium phosphide, silicon germanium carbide, gallium arsenic phosphide, gallium indium phosphide, combinations of these, and the like, may also be used. Additionally, the substrate **202** may be a silicon-on-insulator (SOI) substrate. Generally, an SOI substrate includes a layer of a semiconductor material such as epitaxial silicon, germanium, silicon germanium, SOI, silicon germanium on insulator (SGOI), or combinations thereof. The substrate **202** is, in one alternative embodiment, based on an insulating core such as a fiberglass reinforced resin core. One example core material is fiberglass resin such as FR4. Alternatives for the core material include bismaleimide-triazine (BT) resin, or alternatively, other printed circuit board (PCB) materials or films. Build up films such as Ajinomoto build-up film (ABF) or other laminates may be used for the substrate **202**.

(69) The substrate **202** may include active and passive devices (not shown). A wide variety of

devices such as transistors, capacitors, resistors, combinations of these, and the like may be used to generate the structural and functional requirements of the design for the second package components **200**. The devices may be formed using any suitable methods.

(70) The substrate **202** may also include metallization layers (not shown) and the conductive vias **208**. The metallization layers may be formed over the active and passive devices and are designed to connect the various devices to form functional circuitry. The metallization layers may be formed of alternating layers of dielectric material (e.g., low-k dielectric material) and conductive material (e.g., copper) with vias interconnecting the layers of conductive material and may be formed through any suitable process (such as deposition, damascene, dual damascene, or the like). In some embodiments, the substrate **202** is substantially free of active and passive devices.

(71) The substrate **202** may have bond pads **204** on a first side of the substrate **202** to couple to the stacked dies **210**, and bond pads **206** on a second side of the substrate **202**, the second side being opposite the first side of the substrate **202**, to couple to the conductive connectors **152**. In some embodiments, the bond pads **204** and **206** are formed by forming recesses (not shown) into dielectric layers (not shown) on the first and second sides of the substrate **202**. The recesses may be formed to allow the bond pads **204** and **206** to be embedded into the dielectric layers. In other embodiments, the recesses are omitted as the bond pads **204** and **206** may be formed on the dielectric layer. In some embodiments, the bond pads **204** and **206** include a thin seed layer (not shown) made of copper, titanium, nickel, gold, palladium, the like, or a combination thereof. The conductive material of the bond pads **204** and **206** may be deposited over the thin seed layer. The conductive material may be formed by an electro-chemical plating process, an electroless plating process, CVD, atomic layer deposition (ALD), PVD, the like, or a combination thereof. In an embodiment, the conductive material of the bond pads **204** and **206** is copper, tungsten, aluminum, silver, gold, the like, or a combination thereof.

(72) In some embodiments, the bond pads **204** and the bond pads **206** are UBMs that include three layers of conductive materials, such as a layer of titanium, a layer of copper, and a layer of nickel. Other arrangements of materials and layers, such as an arrangement of chrome/chrome-copper alloy/copper/gold, an arrangement of titanium/titanium tungsten/copper, or an arrangement of copper/nickel/gold, may be utilized for the formation of the bond pads **204** and **206**. Any suitable materials or layers of material that may be used for the bond pads **204** and **206** are fully intended to be included within the scope of the current application. In some embodiments, the conductive vias **208** extend through the substrate **202** and couple at least one of the bond pads **204** to at least one of the bond pads **206**.

(73) In the illustrated embodiment, the stacked dies **210** are coupled to the substrate **202** by wire bonds **212**, although other connections may be used, such as conductive bumps. In an embodiment, the stacked dies **210** are stacked memory dies. For example, the stacked dies **210** may be memory dies such as low-power (LP) double data rate (DDR) memory modules, such as LPDDR1, LPDDR2, LPDDR3, LPDDR4, or the like memory modules.

(74) The stacked dies **210** and the wire bonds **212** may be encapsulated by a molding material **214**. The molding material **214** may be molded on the stacked dies **210** and the wire bonds **212**, for example, using compression molding. In some embodiments, the molding material **214** is a molding compound, a polymer, an epoxy, silicon oxide filler material, the like, or a combination thereof. A curing process may be performed to cure the molding material **214**; the curing process may be a thermal curing, a UV curing, the like, or a combination thereof.

(75) In some embodiments, the stacked dies **210** and the wire bonds **212** are buried in the molding material **214**, and after the curing of the molding material **214**, a planarization step, such as a grinding, is performed to remove excess portions of the molding material **214** and provide a substantially planar surface for the second package components **200**.

(76) After the second package components **200** are formed, the second package components **200** are mechanically and electrically bonded to the first package component **100** by way of the

conductive connectors **152**, the bond pads **206**, and a metallization pattern of the back-side redistribution structure **106**. In some embodiments, the stacked dies **210** may be coupled to the integrated circuit dies **50A** and **50B** through the wire bonds **212**, the bond pads **204** and **206**, the conductive vias **208**, the conductive connectors **152**, the back-side redistribution structure **106**, the through vias **116**, and the front-side redistribution structure **122**.

(77) In some embodiments, a solder resist (not shown) is formed on the side of the substrate **202** opposing the stacked dies **210**. The conductive connectors **152** may be disposed in openings in the solder resist to be electrically and mechanically coupled to conductive features (e.g., the bond pads **206**) in the substrate **202**. The solder resist may be used to protect areas of the substrate **202** from external damage.

(78) In some embodiments, the conductive connectors **152** have an epoxy flux (not shown) formed thereon before they are reflowed with at least some of the epoxy portion of the epoxy flux remaining after the second package components **200** are attached to the first package component **100**.

(79) In some embodiments, an underfill (not shown) is formed between the first package component **100** and the second package components **200**, surrounding the conductive connectors **152**. The underfill may reduce stress and protect the joints resulting from the reflowing of the conductive connectors **152**. The underfill may be formed by a capillary flow process after the second package components **200** are attached, or may be formed by a suitable deposition method before the second package components **200** are attached. In embodiments where the epoxy flux is formed, it may act as the underfill.

(80) In FIG. **21A**, a singulation process is performed by sawing along scribe line regions, e.g., between the first package region **100A** and the second package region **100B**. The sawing singulates the first package region **100A** from the second package region **100B**. The resulting, singulated device stack is from one of the first package region **100A** or the second package region **100B**. In some embodiments, the singulation process is performed after the second package components **200** are coupled to the first package component **100**. In other embodiments (not shown), the singulation process is performed before the second package components **200** are coupled to the first package component **100**, such as after the carrier substrate **102** is de-bonded and the conductive connectors **152** are formed.

(81) Each singulated first package component **100** may then be mounted to a package substrate **300** using the conductive connectors **150**. The package substrate **300** includes a substrate core **302** and bond pads **304** over the substrate core **302**. The substrate core **302** may be made of a semiconductor material such as silicon, germanium, diamond, or the like. Alternatively, compound materials such as silicon germanium, silicon carbide, gallium arsenic, indium arsenide, indium phosphide, silicon germanium carbide, gallium arsenic phosphide, gallium indium phosphide, combinations of these, and the like, may also be used. Additionally, the substrate core **302** may be an SOI substrate. Generally, an SOI substrate includes a layer of a semiconductor material such as epitaxial silicon, germanium, silicon germanium, SOI, SGOI, or combinations thereof. The substrate core **302** is, in one alternative embodiment, based on an insulating core such as a fiberglass reinforced resin core. One example core material is fiberglass resin such as FR4. Alternatives for the core material include bismaleimide-triazine BT resin, or alternatively, other PCB materials or films. Build up films such as ABF or other laminates may be used for substrate core **302**.

(82) The substrate core **302** may include active and passive devices (not shown). A wide variety of devices such as transistors, capacitors, resistors, combinations of these, and the like may be used to generate the structural and functional requirements of the design for the device stack. The devices may be formed using any suitable methods.

(83) The substrate core **302** may also include metallization layers and vias (not shown), with the bond pads **304** being physically and/or electrically coupled to the metallization layers and vias. The metallization layers may be formed over the active and passive devices and are designed to connect

the various devices to form functional circuitry. The metallization layers may be formed of alternating layers of dielectric material (e.g., low-k dielectric material) and conductive material (e.g., copper) with vias interconnecting the layers of conductive material and may be formed through any suitable process (such as deposition, damascene, dual damascene, or the like). In some embodiments, the substrate core **302** is substantially free of active and passive devices.

(84) In some embodiments, the conductive connectors **150** are reflowed to attach the first package component **100** to the bond pads **304**. The conductive connectors **150** electrically and/or physically couple the package substrate **300**, including metallization layers in the substrate core **302**, to the first package component **100**. In some embodiments, a solder resist **306** is formed on the substrate core **302**. The conductive connectors **150** may be disposed in openings in the solder resist **306** to be electrically and mechanically coupled to the bond pads **304**. The solder resist **306** may be used to protect areas of the substrate **202** from external damage.

(85) The conductive connectors **150** may have an epoxy flux (not shown) formed thereon before they are reflowed with at least some of the epoxy portion of the epoxy flux remaining after the first package component **100** is attached to the package substrate **300**. This remaining epoxy portion may act as an underfill to reduce stress and protect the joints resulting from reflowing the conductive connectors **150**. In some embodiments, an underfill **308** may be formed between the first package component **100** and the package substrate **300** and surrounding the conductive connectors **150**. The underfill **308** may be formed by a capillary flow process after the first package component **100** is attached or may be formed by a suitable deposition method before the first package component **100** is attached.

(86) In some embodiments, passive devices (e.g., surface mount devices (SMDs), not shown) may also be attached to the first package component **100** (e.g., to the UBMs **138**) or to the package substrate **300** (e.g., to the bond pads **304**). For example, the passive devices may be bonded to a same surface of the first package component **100** or the package substrate **300** as the conductive connectors **150**. The passive devices may be attached to the package component **100** prior to mounting the first package component **100** on the package substrate **300**, or may be attached to the package substrate **300** prior to or after mounting the first package component **100** on the package substrate **300**.

(87) The first package component **100** may be implemented in other device stacks. For example, a PoP structure is shown, but the first package component **100** may also be implemented in a Flip Chip Ball Grid Array (FCBGA) package. In such embodiments, the first package component **100** is mounted to a substrate such as the package substrate **300**, but the second package component **200** is omitted. Instead, a lid or heat spreader may be attached to the first package component **100**. When the second package component **200** is omitted, the back-side redistribution structure **106** and through vias **116** may also be omitted.

(88) Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or the 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

(89) FIG. **21B** illustrates a detailed cross-sectional view of region **101** as illustrated in FIG. **21A**, in accordance with some embodiments. The dielectric slot **111** is over the conductive via **117** that extends from the through via **116**. The first width $W_{sub.1}$ of the dielectric slot **111** is larger than the second width $W_{sub.2}$ of the conductive via **117**.

(90) FIG. **21C** illustrates a top-down view of the structure at a level of the metallization pattern **110**, in accordance with some embodiments. As shown in FIG. **21C**, the dielectric slot **111** overlaps

the through-via **116** (shown as a dashed circle) and the conductive via **117** (shown as a dashed circle) in the top-down view.

(91) FIGS. **22A** through **25** illustrate cross-sectional views of intermediate steps during a process for forming a third package component **400**, in accordance with some other embodiments. Elements of the third package component **400** may be similar to the first package component **100** described above in reference to FIGS. **2-19** where like reference numerals indicate like elements formed using like processes. As discussed in greater detail below, a back-side redistribution structure **406** is formed to include an adhesion layer. The adhesion layer may help reduce the stress incurred as a result of through vias being subsequently formed over the back-side redistribution structure **406**, thereby preventing or reducing delamination between the various layers of the back-side redistribution structure **406**.

(92) Referring first to FIGS. **22A** and **22B**, there is illustrated the formation of the dielectric layer **108** over the release layer **104**, and the metallization pattern **110** over the dielectric layer **108**. FIG. **22B** illustrates a detailed cross-sectional view of region **401** as illustrated in FIG. **22A**. The dielectric layer **108** and the metallization pattern **110** may be formed using similar methods and materials as described above with respect to FIGS. **3A-3C**, and the details are not repeated herein. In some embodiments, conductive features of the metallization pattern **110** extend underneath subsequently formed through vias (see, e.g., through vias **116** in FIG. **25**).

(93) In FIGS. **23A-23B**, an adhesion layer **402** is formed over the metallization pattern **110**. The adhesion layer **402** increases adhesion between the metallization pattern **110** and a subsequently formed dielectric layer (see below, FIG. **24**) and may reduce or prevent delamination between the various metallization patterns and dielectric layers of the back-side redistribution structure **406**. Including the adhesion layer **402** in the back-side redistribution structure **406** may reduce areas of delamination between the metallization pattern **110** and the dielectric layer **112** underneath through vias **116** by a factor in a range of 50% to 60%.

(94) The adhesion layer **402** may be formed by any acceptable deposition process, such as spin coating, CVD, laminating, the like, or a combination thereof. In some embodiments, the adhesion layer **402** comprises a polymer containing 1-Pyrroline, imidazole, the like, or a combination thereof.

(95) In some embodiments, the adhesion layer **402** is formed to a first thickness $T_{sub.1}$ in a range of 30 nm to 80 nm, which is advantageous for reducing or preventing delamination between the various metallization patterns and dielectric layers. In some embodiments, as illustrated in accordance with FIG. **23A**, the adhesion layer **402** covers exposed surfaces of the metallization pattern **110** and the dielectric layer **108**.

(96) In FIG. **24**, following from FIGS. **23A-23B**, the back-side redistribution structure **406** is completed by forming the dielectric layer **112**, the metallization pattern **113**, and the dielectric layer **114**. In some embodiments, the adhesion layer **402** is patterned together with the dielectric layer **112** using, e.g., an acceptable photolithography process. Conductive vias of the metallization pattern **113** are formed through the dielectric layer **112** and the adhesion layer **402** to physically and electrically couple with the metallization pattern **110**. Openings **115** are formed through the dielectric layer **114** to expose portions of the metallization pattern **113**. The dielectric layer **112**, the metallization pattern **113**, the dielectric layer **114**, and the openings **115** may be formed with similar methods and materials as described above with respect to FIGS. **4A-6A**, and the details are not repeated herein. In some embodiments, an additional adhesion layer **402** is formed over the metallization pattern **113**. In embodiments in which the back-side redistribution structure **406** has additional levels of metallization patterns and dielectric layers, additional adhesion layers may be formed over any of the metallization patterns.

(97) In FIG. **25**, through vias **116** are formed in the openings **115** and extending away from the topmost dielectric layer of the back-side redistribution structure **406** (e.g., the dielectric layer **112**). The through vias **116** may be formed with similar methods and materials as described above with

respect to FIGS. 7A-7B. Subsequent steps of manufacturing the third package component **400** may be similar to steps for manufacturing the first package component **100** as described above with respect to FIGS. 8A-19, and the details are not repeated herein.

(98) FIG. 26A illustrates a device stack formed from a singulated third package component **400** that has been coupled to a second package component **200** and mounted on a package substrate **300**, in accordance with some embodiments. FIG. 26B illustrates a detailed cross-sectional view of region **401** as illustrated in FIG. 26A, in accordance with some embodiments. The device stack illustrated in FIGS. 26A-26B may be formed from the third package component **400** using similar methods and materials as described above with respect to FIGS. 20-21B, and the details are not repeated herein. The back-side redistribution structure **406** includes an adhesion layer **402** disposed between the metallization pattern **110** and the dielectric layer **112**. FIG. 26C illustrates a top-down view of the structure at a level of the adhesion layer **402**, in accordance with some embodiments. As shown in FIG. 26C, the adhesion layer **402** overlaps the through-via **116** (shown as a dashed circle) and the conductive via **117** (shown as a dashed circle) in the top-down view.

(99) FIGS. 27A through 31 illustrate cross-sectional views of intermediate steps during a process for forming a fourth package component **500**, in accordance with some other embodiments. The fourth package component **500** includes a back-side redistribution structure **506** having dielectric layers **508** and **512** with increased thicknesses or adjusted relative thicknesses. The fourth package component **500** may be similar to the first package component **100** described above in reference to FIGS. 2-19 where like reference numerals indicate like elements formed using like processes.

(100) In FIGS. 27A through 30, a back-side redistribution structure **506** is formed on the release layer **104**. In the embodiment shown, the back-side redistribution structure **506** includes one or more dielectric layers and metallization patterns (sometimes referred to as redistribution layers or redistribution lines) between adjacent ones of the dielectric layers. The back-side redistribution structure **506** includes dielectric layers with increased respective thicknesses and adjusted relative thicknesses with respect to each other. The increased respective thicknesses of the dielectric layers and the adjusted relative thicknesses of the dielectric layers with respect to each other may reduce the stress between various layers, such as between the layers of the metallization patterns and the dielectric layers of the back-side redistribution structure, thereby reducing delamination issues.

(101) FIG. 27A illustrates the formation of the dielectric layer **508** over the release layer **104**. FIG. 27B illustrates a detailed cross-sectional view of region **501** as illustrated in FIG. 27A. The dielectric layer **508** may be formed using similar methods and materials as described above for the dielectric layer **108** with respect to FIGS. 3A-3C, and the details are not repeated herein. In some embodiments, the dielectric layer **508** is formed to a second thickness $T_{sub.2}$ in a range of 7.5 μm to 15 μm .

(102) FIGS. 28A-28B illustrate the formation of the metallization pattern **110**. The metallization pattern **110** may be formed using similar methods and materials as described above with respect to FIGS. 4A-4C, and the details are not repeated herein. In some embodiments, the metallization pattern **110** is not formed with regions **109** free of conductive material underneath subsequently formed through vias **116** (see below, FIG. 31).

(103) FIGS. 29A-29B illustrate the formation of the dielectric layer **512**. The dielectric layer **512** may be formed using similar methods and materials as described above for the dielectric layer **112** with respect to FIGS. 4A-4B, and the details are not repeated herein. In some embodiments, the dielectric layer **512** is formed to a third thickness $T_{sub.3}$ in a range of 7.5 μm to 15 μm .

(104) By adjusting the ratio of the second thickness $T_{sub.2}$ of the dielectric layer **512** to the third thickness $T_{sub.3}$, stress between the metallization pattern **110** and the dielectric layer **512** at positions underneath the subsequently formed through vias **116** may be reduced. This may reduce or prevent areas of delamination between the metallization pattern **110** and the dielectric layer **512** underneath the subsequently formed through vias **116**. In some embodiments, the ratio of the second thickness $T_{sub.2}$ to the third thickness $T_{sub.3}$ is 1 or greater, such as in a range of 1 to 3,

which is advantageous for reducing or preventing delamination between the metallization pattern **110** and the dielectric layer **512**. As an example, the ratio of $T_{sub.2}:T_{sub.3}$ being in a range of 1 to 3 may reduce stress on the dielectric layer **512** by up to 18% during high temperature processes such as subsequent curing of the encapsulant **120** (see above, FIGS. **9A-9B**) performed at about 220° C. The ratio of $T_{sub.2}:T_{sub.3}$ being less than 1 may not sufficiently reduce stress between the metallization pattern **110** and the dielectric layer **512**. The ratio of $T_{sub.2}:T_{sub.3}$ being greater than 3 may be disadvantageous by leading to increased package warpage or jagged edges of openings for conductive connectors formed through the dielectric layer **512** after, e.g., laser drilling (see above, FIG. **18**).

(105) In FIG. **30A** and **30B**, the back-side redistribution structure **506** is completed by forming the metallization pattern **113** and the dielectric layer **114**. Openings **115** are formed through the dielectric layer **114** to expose portions of the metallization pattern **113**. The metallization pattern **113**, the dielectric layer **114**, and the openings **115** may be formed with similar methods and materials as described above with respect to FIGS. **5A-6A**, and the details are not repeated herein.

(106) In FIG. **31**, through vias **116** are formed in the openings **115** and extending away from the topmost dielectric layer of the back-side redistribution structure **506** (e.g., the dielectric layer **112**). The through vias **116** may be formed with similar methods and materials as described above with respect to FIGS. **7A-7B**. Subsequent steps of manufacturing the fourth package component **500** may be similar to steps for manufacturing the first package component **100** as described above with respect to FIGS. **8A-19**, and the details are not repeated herein.

(107) FIG. **32A** illustrates a device stack formed from a singulated fourth package component **500** that has been coupled to a second package component **200** and mounted on a package substrate **300**, in accordance with some embodiments. FIG. **32B** illustrates a detailed cross-sectional view of region **501** as illustrated in FIG. **32A**, in accordance with some embodiments. The device stack illustrated in FIGS. **32A-32B** may be formed from the fourth package component **500** using similar methods and materials as described above with respect to FIGS. **20-21B**, and the details are not repeated herein. The back-side redistribution structure **506** includes a dielectric layer **508** with a second thickness $T_{sub.2}$ and a dielectric layer **512** with a third thickness $T_{sub.3}$. In some embodiments, the ratio of the second thickness $T_{sub.2}$ to the third thickness $T_{sub.3}$ is in a range of 1 to 3.

(108) FIGS. **33** through **36** illustrate cross-sectional views of regions similar to region **101** (see above, FIGS. **21A-21B**), region **401** (see above, FIGS. **26A-26B**), and region **501** (see above, FIGS. **32A-32B**) in embodiments having combinations of dielectric slots **111**, adhesion layers **402**, and dielectric layers **508** and **512** with increased thicknesses or adjusted relative thicknesses. FIG. **33** illustrates an embodiment with a dielectric slot **111** in the metallization pattern **110** with in an adhesion layer **402** over the metallization pattern **110**. FIG. **34** illustrates an embodiment with a dielectric slot **111** in the metallization pattern **110** in combination with the dielectric layers **508** and **512** with increased thicknesses or adjusted relative thicknesses. FIG. **35** illustrates an embodiment with an adhesion layer **402** over the metallization pattern **110** in combination with the dielectric layers **508** and **512** with increased thicknesses or adjusted relative thicknesses. FIG. **36** illustrates an embodiment with a dielectric slot **111** in the metallization pattern **110** with the adhesion layer **402** over the metallization pattern, wherein dielectric layers **508** and **512** have increased thicknesses or adjusted relative thicknesses.

(109) FIG. **37A** illustrates a device stack formed from a singulated fifth package component **600** that has been coupled to a second package component **200** and mounted on a package substrate **300**, in accordance with some embodiments. FIG. **37B** illustrates a detailed cross-sectional view of region **601** as illustrated in FIG. **37A**, in accordance with some embodiments. The fifth package component **600** includes a back-side redistribution structure **606** with four dielectric layers and three metallization patterns, which may be formed using similar methods and materials as the back-side redistribution structure **106** as described above with respect to FIGS. **3A-6B** with the addition

of one dielectric layer and one metallization pattern **610**. The device stack illustrated in FIGS. **37A-37B** may be formed from the fifth package component **600** using similar methods and materials as described above with respect to FIGS. **20-21B**, and the details are not repeated herein. As shown in FIG. **32B**, the back-side redistribution structure **606** includes a metallization pattern **610** above the dielectric layer **108**, and conductive material of the metallization pattern **610** may be above the dielectric slot **111**, over the footprint of the conductive via **117**. FIG. **37C** illustrates a top-down view of the structure at a level of the metallization pattern **610**, in accordance with some embodiments. As shown in FIG. **37C**, conductive material of the metallization pattern **610** overlaps the dielectric slot **111** (shown as a dashed circle), the through-via **116** (shown as a dashed circle), and the conductive via **117** (shown as a dashed circle) in the top-down view.

(110) Embodiments may achieve advantages, such as reducing or preventing disadvantageous delamination between metallization patterns and dielectric layers of a back-side redistribution structure. Dielectric slots may be included in a metallization pattern below respective footprints of the through vias. An adhesion layer may be formed over a metallization pattern to increase adhesion with a subsequently formed dielectric layer. Relative thicknesses of dielectric layers of the back-side redistribution structure may be adjusted.

(111) In accordance with an embodiment, a semiconductor package includes: a back-side redistribution structure, the back-side redistribution structure including: a first dielectric layer; a second dielectric layer on the first dielectric layer; a first metallization pattern between the first dielectric layer and the second dielectric layer, wherein the second dielectric layer extends through the first metallization pattern to form a dielectric slot; and a second metallization pattern, wherein the second dielectric layer is between the first metallization pattern and the second metallization pattern; a front-side redistribution structure; an encapsulant between the back-side redistribution structure and the front-side redistribution structure; and a through via extending through the encapsulant, the through via being physically coupled with the second metallization pattern, wherein the dielectric slot overlaps the through via in a top-down view. In an embodiment, the dielectric slot is in a dummy pattern of the first metallization pattern. In an embodiment, the dielectric slot has a first surface area in the top-down view, a rectangular dielectric region in the dummy pattern has a second surface area in the top-down view, and the first surface area is larger than the second surface area. In an embodiment, wherein the dielectric slot has a round shape in a top-down view. In an embodiment, the through via includes a conductive via extending into the back-side redistribution structure, the dielectric slot overlapping the conductive via in the top-down view. In an embodiment, the dielectric slot has a first width, the conductive via has a second width, and the first width is greater than the second width. In an embodiment, the back-side redistribution structure further includes a third metallization pattern, wherein the first dielectric layer is between the third metallization pattern and the first metallization pattern, wherein conductive material of the third metallization pattern overlaps the dielectric slot in the top-down view. In an embodiment, the back-side redistribution structure further includes an adhesion layer between the first metallization pattern and the second dielectric layer.

(112) In accordance with another embodiment, a semiconductor package includes: a front-side redistribution structure; a back-side redistribution structure, the back-side redistribution structure including: a first dielectric layer; a first metallization pattern on the first dielectric layer; an adhesion layer on the first metallization pattern, wherein the first metallization pattern is between the adhesion layer and the first dielectric layer, wherein a portion of the adhesion layer overlaps the through via in a top-down view; a second dielectric layer on the adhesion layer, wherein the adhesion layer is between the second dielectric layer and the first metallization pattern; and a second metallization pattern on the second dielectric layer, wherein the second dielectric layer is between the second metallization pattern and the adhesion layer; an integrated circuit die electrically coupled to the front-side redistribution structure, the integrated circuit die being between the front-side redistribution structure and the back-side redistribution structure; an

encapsulant extending around the integrated circuit die; and a through via extending through the encapsulant, the through via electrically coupling the front-side redistribution structure to the back-side redistribution structure. In an embodiment, the adhesion layer includes 1-Pyrroline. In an embodiment, a conductive via of the second metallization pattern extends through the adhesion layer to physically contact the first metallization pattern. In an embodiment, the first dielectric layer has a first thickness, the second dielectric layer has a second thickness, and a ratio of the first thickness to the second thickness is 1 or greater. In an embodiment, the back-side redistribution structure further includes a dielectric slot through the first metallization pattern, the dielectric slot overlapping the through via in a top-down view.

(113) In accordance with yet another embodiment, a method of manufacturing a semiconductor package includes: depositing a first dielectric layer over a carrier substrate; forming a first metallization pattern over the first dielectric layer, wherein the first metallization pattern has a first opening exposing the first dielectric layer; depositing a second dielectric layer over the first metallization pattern, wherein depositing the second dielectric layer forms a dielectric slot through the first metallization pattern by filling the first opening; forming a second metallization pattern over the second dielectric layer; depositing a third dielectric layer over the second metallization pattern; and forming a through via over the third dielectric layer, wherein the dielectric slot is laterally under the through via. In an embodiment, forming the through via includes forming a conductive via through the third dielectric layer, the conductive via overlying the dielectric slot. In an embodiment, the dielectric slot has a first width, the conductive via has a second width, and the first width is greater than the second width. In an embodiment, the method further includes forming an adhesion layer over the first metallization pattern, wherein the second dielectric layer is subsequently deposited over the adhesion layer, wherein forming the second metallization pattern includes forming a second opening through the second dielectric layer and the adhesion layer. In an embodiment, the adhesion layer includes a polymer. In an embodiment, the first dielectric layer has a first thickness, the second dielectric layer has a second thickness, and a ratio of the first thickness to the second thickness is in a range of 1 to 3. In an embodiment, the method further includes: adhering an integrated circuit die to the third dielectric layer; encapsulating the integrated circuit die and the through via with an encapsulant; and forming a front-side redistribution structure over the integrated circuit die, the through via, and the encapsulant.

(114) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor package, comprising: a back-side redistribution structure, the back-side redistribution structure comprising: a first dielectric layer; a second dielectric layer on the first dielectric layer; a first metallization pattern between the first dielectric layer and the second dielectric layer, wherein the second dielectric layer extends through the first metallization pattern to form a dielectric slot; and a second metallization pattern, wherein the second dielectric layer is between the first metallization pattern and the second metallization pattern; a front-side redistribution structure; an encapsulant between the back-side redistribution structure and the front-side redistribution structure; and a through via extending through the encapsulant, the through via being physically coupled with the second metallization pattern by a conductive via extending into

the back-side redistribution structure, wherein the dielectric slot overlaps the through via in a top-down view, and wherein the conductive via is surrounded by the dielectric slot in the top-down view.

2. The semiconductor package of claim 1, wherein the dielectric slot is in a dummy pattern of the first metallization pattern.

3. The semiconductor package of claim 2, wherein the dielectric slot has a first surface area in the top-down view, a rectangular dielectric region in the dummy pattern has a second surface area in the top-down view, and the first surface area is larger than the second surface area.

4. The semiconductor package of claim 1, wherein the dielectric slot has a round shape in a top-down view.

5. The semiconductor package of claim 1, wherein the dielectric slot has a first width, the conductive via has a second width, and the first width is greater than the second width.

6. The semiconductor package of claim 1, wherein the back-side redistribution structure further comprises a third metallization pattern, wherein the first dielectric layer is between the third metallization pattern and the first metallization pattern, wherein conductive material of the third metallization pattern overlaps the dielectric slot in the top-down view.

7. The semiconductor package of claim 1, wherein the back-side redistribution structure further comprises an adhesion layer between the first metallization pattern and the second dielectric layer.

8. The semiconductor package of claim 7, wherein the adhesion layer comprises imidazole.

9. A semiconductor package, comprising: a front-side redistribution structure; a back-side redistribution structure, the back-side redistribution structure comprising: a first dielectric layer; a first metallization pattern on the first dielectric layer; an adhesion layer on the first metallization pattern, wherein the first metallization pattern is between the adhesion layer and the first dielectric layer; a second dielectric layer on the adhesion layer, wherein the adhesion layer is between the second dielectric layer and the first metallization pattern; and a second metallization pattern on the second dielectric layer, wherein the second dielectric layer is between the second metallization pattern and the adhesion layer; an integrated circuit die electrically coupled to the front-side redistribution structure, the integrated circuit die being between the front-side redistribution structure and the back-side redistribution structure; an encapsulant extending around the integrated circuit die; and a through via extending through the encapsulant, the through via electrically coupling the front-side redistribution structure to the back-side redistribution structure, wherein a portion of the adhesion layer overlaps the through via in a top-down view.

10. The semiconductor package of claim 9, wherein the adhesion layer comprises 1-Pyrroline.

11. The semiconductor package of claim 9, wherein a conductive via of the second metallization pattern extends through the adhesion layer to physically contact the first metallization pattern.

12. The semiconductor package of claim 9, wherein the first dielectric layer has a first thickness, the second dielectric layer has a second thickness, and a ratio of the first thickness to the second thickness is 1 or greater.

13. The semiconductor package of claim 9, wherein the back-side redistribution structure further comprises a dielectric slot through the first metallization pattern, the dielectric slot overlapping the through via in a top-down view.

14. A semiconductor package, comprising: a first redistribution structure, the first redistribution structure comprising: a first dielectric layer; a first conductive feature and a second conductive feature on the first dielectric layer; a second dielectric layer, wherein a first portion of the second dielectric layer is on the first conductive feature and the second conductive feature, and wherein a second portion of the second dielectric layer is between the first conductive feature and the second conductive feature; and a third conductive feature on the second dielectric layer; and a conductive via connected to the third conductive feature, wherein the conductive via is laterally underneath the second portion of the second dielectric layer, and wherein the second portion of the second dielectric layer has a first width and the conductive via has a second width smaller than the first

width.

15. The semiconductor package of claim 14, further comprising an adhesion layer, wherein the adhesion layer is between the first conductive feature and the second dielectric layer, and wherein the adhesion layer is between the second conductive feature and the second dielectric layer.

16. The semiconductor package of claim 15, wherein the adhesion layer is between the first dielectric layer and the second dielectric layer.

17. The semiconductor package of claim 15, wherein the adhesion layer comprises a polymer.

18. The semiconductor package of claim 14, wherein the first dielectric layer has a first thickness and the second dielectric layer has a second thickness, and wherein a ratio of the first thickness to the second thickness is in a range from 1 to 3.

19. The semiconductor package of claim 14, further comprising a second redistribution structure and an encapsulant between the first redistribution structure and the second redistribution structure, wherein the conductive via extends through the encapsulant.

20. The semiconductor package of claim 14, wherein the second portion of the second dielectric layer has a circular shape in a top-down view.
