

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408391
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Song; Inhyun et al.

Display device including a sensing layer for sensing an external input device and method of driving the same

Abstract

A semiconductor device includes: a substrate including an active region extending in a first direction; a gate electrode extending in a second direction and intersecting the active region, the gate electrode including first electrode layer(s) and a second electrode layer; channel layers spaced apart from each other in a third direction and at least partially surrounded by the gate electrode; source/drain regions, with at least one source/drain region on each side of the gate electrode and electrically connected to the channel layers; and air gap regions in the second electrode layer between the channel layers and between a lowermost channel layer and the active region in the third direction. The first electrode layer(s) or the second electrode layer has a first thickness between adjacent ones of the channel layers in the third direction, and has a second thickness greater than the first thickness on side surfaces of the channel layers.

Inventors: Song; Inhyun (Suwon-si, KR), Kwon; Ohseong (Hwaseong-si, KR), Yang; Junggil (Hwaseong-si, KR), Jung; Jooho (Suwon-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 86145822

Assignee: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Appl. No.: 17/814876

Filed: July 26, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230139314 A1	May. 04, 2023

Foreign Application Priority Data

KR	10-2021-0149072	Nov. 02, 2021
----	-----------------	---------------

Publication Classification

Int. Cl.: **H10D62/10** (20250101); **H10D30/43** (20250101); **H10D30/67** (20250101); **H10D84/03** (20250101); **H10D84/83** (20250101); H10D30/01 (20250101); H10D64/01 (20250101); H10D84/01 (20250101)

U.S. Cl.:

CPC **H10D62/115** (20250101); **H10D30/43** (20250101); **H10D30/6735** (20250101); **H10D30/6757** (20250101); **H10D84/83** (20250101); H10D30/014 (20250101); H10D64/01 (20250101); H10D64/017 (20250101); H10D84/0128 (20250101); H10D84/0151 (20250101); H10D84/038 (20250101)

Field of Classification Search

CPC: H10D (30/43); H10D (30/435); H10D (30/501); H10D (30/502); H10D (30/503); H10D (30/504); H10D (30/506); H10D (30/507); H10D (30/508); H10D (30/509); H10D (30/6735); H10D (30/797); H10D (30/6219); H10D (30/6211); H10D (30/01); H10D (30/014); H10D (30/0191); H10D (30/0193); H10D (30/0194); H10D (30/0195); H10D (30/0196); H10D (30/0197); H10D (30/0198); H10D (30/0273); H10D (62/115); H10D (62/364); H10D (62/121); H10D (62/151); H10D (62/822); H10D (62/83); H10D (64/01); H10D (64/017); H10D (64/256); H10D (64/254); H10D (64/257); H10D (64/666); H10D (84/83); H10D (84/8311); H10D (84/8312); H10D (84/83135); H10D (84/83138); H10D (84/8314); H10D (84/8316); H10D (84/832); H10D (84/833); H10D (84/834); H10D (84/835); H10D (84/836); H10D (84/937); H10D (84/839); H10D (84/0153); H10D (84/128); H10D (84/038); H10D (84/01); H10D (84/014); H10D (84/0142); H10D (84/0158); H10D (84/0151); H10D (84/02); H10D (84/032); H10D (84/035); H10D (84/05); H10D (84/07); H10D (84/08); B82Y (10/00)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9899416	12/2017	Kim et al.	N/A	N/A
10490559	12/2018	Ando et al.	N/A	N/A
10896816	12/2020	Bi et al.	N/A	N/A
10930649	12/2020	Kang et al.	N/A	N/A
2019/0157414	12/2018	Ando	N/A	H10D 62/121
2019/0305104	12/2018	Xie	N/A	H10D 62/121
2020/0006356	12/2019	Ando	N/A	B82Y 10/00
2020/0083352	12/2019	Chanemougame	N/A	H10D 30/6757
2021/0134794	12/2020	Huang et al.	N/A	N/A
2021/0202709	12/2020	Lee et al.	N/A	N/A
2022/0069078	12/2021	Yu	N/A	H10D 64/251
2022/0115514	12/2021	Jung	N/A	H10D 62/121
2022/0254781	12/2021	Song et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
------------	------------------	---------	-----

Primary Examiner: Trinh; Michael M

Attorney, Agent or Firm: Myers Bigel, P.A.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

(1) This application claims the benefit below 35 USC 119(a) of Korean Patent Application No. 10-2021-0149072 filed on Nov. 2, 2021, in the Korean Intellectual Property Office, the entire disclosure of which is incorporated herein by reference for all purposes.

BACKGROUND

(2) The present disclosure relates to a semiconductor device.

(3) As demand for high performance, high speed, and/or multifunctionality of semiconductor devices increase, the degree of integration of semiconductor devices is increasing. In manufacturing a semiconductor device having a fine pattern corresponding to the trend for high integration of semiconductor devices, it may be beneficial to implement patterns having a fine width or a fine separation distance. In addition, in order to reduce limitations in operating characteristics due to size reductions of planar metal oxide semiconductor FETs (MOSFETs), efforts are being made to develop a semiconductor device having a channel including a three-dimensional structure.

SUMMARY

(4) Example embodiments provide a semiconductor device having improved electrical characteristics and reliability.

(5) According to example embodiments, a semiconductor device comprises: a substrate including an active region extending in a first direction; a gate electrode extending in a second direction and intersecting the active region on the substrate, the gate electrode comprising at least one first electrode layer and a second electrode layer; a plurality of channel layers on the active region and spaced apart from each other in a third direction perpendicular to an upper surface of the substrate the plurality of channel layers at least partially surrounded by the gate electrode; a plurality of source/drain regions, with at least one source/drain region on each side of the gate electrode, the plurality of channel layers electrically connected to the plurality of channel layers; and one or more air gap regions located in the second electrode layer between the plurality of channel layers and between a lowermost channel layer of the plurality of channel layers and the active region in the third direction. The at least one first electrode layer or the second electrode layer has a first thickness between adjacent ones of the plurality of channel layers in the third direction, and has a second thickness on side surfaces of the plurality of channel layers, wherein the second thickness is greater than the first thickness.

(6) According to example embodiments, a semiconductor device comprises: a substrate having first and second regions, the substrate comprising an active region on each of the first and second regions, respectively; a first gate electrode on the first region intersecting the active region and comprising at least one first electrode layer and a second electrode layer; a second gate electrode on the second region intersecting the active region and comprising at least one third electrode layer and a fourth electrode layer; a plurality of channel layers on each of the active regions, respectively, the plurality of channel layers spaced apart from each other in a vertical direction perpendicular to an upper surface of the substrate and at least partially surrounded by the first and second gate electrodes, respectively; and one or more air gap regions located in the fourth electrode layer

between at least portions of the plurality of channel layers on the second region in the vertical direction. The at least one third electrode layer comprises a same material as a material of the at least one first electrode layer, and the fourth electrode layer comprises a same material as a material of the second electrode layer, and wherein the at least one first electrode layer has a first thickness on the first region, and the at least one third electrode layer on the second region has a second thickness that is less than the first thickness.

(7) According to example embodiments, a semiconductor device comprises: a substrate comprising an active region; a gate electrode extending on the substrate and intersecting the active region, the gate electrode comprising a first electrode layer; a plurality of channel layers on the active region and spaced apart from each other in a vertical direction perpendicular to an upper surface of the substrate the plurality of channel layers at least partially surrounded by the gate electrode a plurality of source/drain regions, with at least one source/drain region on each side of the gate electrode, the plurality of source/drain regions electrically connected to the plurality of channel layers; and one or more air gap regions located in the gate electrode between the plurality of channel layers in the vertical direction. The first electrode layer surrounds an entirety of each of the one or more air gap regions and has a reduced thickness in a region overlapping the one or more air gap regions in the vertical direction.

Description

BRIEF DESCRIPTION OF DRAWINGS

- (1) The above and other aspects, features, and advantages of the present disclosure will be more clearly understood from the following detailed description, taken in conjunction with the accompanying drawings, in which:
- (2) FIG. 1 is a layout diagram illustrating a semiconductor device according to example embodiments;
- (3) FIG. 2 includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments;
- (4) FIG. 3 is a partially enlarged view illustrating a portion of the semiconductor device of FIG. 2 according to example embodiments;
- (5) FIGS. 4A and 4B are schematic cross-sectional views and partially enlarged views illustrating a semiconductor device according to example embodiments;
- (6) FIG. 5 includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments;
- (7) FIGS. 6A and 6B are a layout view and a schematic cross-sectional view illustrating a semiconductor device according to example embodiments, respectively;
- (8) FIG. 7 includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments;
- (9) FIG. 8 includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments;
- (10) FIG. 9 is a flowchart illustrating a method of manufacturing a semiconductor device according to example embodiments;
- (11) FIGS. 10A to 10H are views illustrating a process sequence to illustrate a method of manufacturing a semiconductor device according to example embodiments; and
- (12) FIGS. 11A to 11G are diagrams illustrating a process sequence to illustrate a method of manufacturing a semiconductor device according to example embodiments.

DETAILED DESCRIPTION

- (13) Hereinafter, example embodiments will be described with reference to the accompanying drawings.

(14) FIG. 1 is a layout diagram illustrating a semiconductor device according to example embodiments. For convenience of description, only some components of the semiconductor device are illustrated in FIG. 1.

(15) FIG. 2 includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments. FIG. 2 illustrates cross-sections taken along lines I-I' and II-II' of FIG. 1.

(16) FIG. 3 is a partially enlarged view illustrating a portion of the semiconductor device of FIG. 2 according to example embodiments. FIG. 3 illustrates an enlarged area 'A' of FIG. 2.

(17) Referring to FIGS. 1 to 3, a semiconductor device **100** may include a substrate **101** including an active region **105**, a channel structure **140** including first to third channel layers **141**, **142** and **143** vertically spaced apart from each other on the active region **105**, a gate structure GS extending through and intersecting the active region **105** and including a gate electrode **170**, source/drain regions **150** in contact with the channel structure **140**, air gap regions AG located in the gate electrode **170**, and contact plugs **180** connected to the source/drain regions **150**. The semiconductor device **100** may further include an isolation layer **110**, inner spacer layers **130**, and an interlayer insulating layer **190**. The gate structure GS includes gate dielectric layers **162**, gate spacer layers **164**, and the gate electrode **170** including the first to third electrode layers **172**, **174**, and **176**.

(18) In the semiconductor device **100**, the active region **105** may have a fin shape, and the gate electrode **170** may be between the active region **105** and the channel structure **140**, between the first to third channel layers **141**, **142**, and **143** of the channel structure **140**, and on the channel structure **140**. Accordingly, the semiconductor device **100** may include a transistor having a multi-bridge channel FET (MBCFET™) structure, which is a gate-all-around field effect transistor.

(19) The substrate **101** may have an upper surface extending in the X-direction and the Y-direction. The substrate **101** may include a semiconductor material, for example, a group IV semiconductor, a group III-V compound semiconductor, or a group II-VI compound semiconductor. For example, the group IV semiconductor may include silicon, germanium, or silicon-germanium. The substrate **101** may be provided as a bulk wafer, an epitaxial layer, a silicon on insulator (SOI) layer, a semiconductor on insulator (SeOI) layer, or the like.

(20) The substrate **101** may include an active region **105** in an upper portion thereof. The active region **105** may be defined by a device isolation layer **110** in the substrate **101** and may extend in a first direction, for example, the X-direction. However, it may be possible to describe the active region **105** as an element separate from the substrate **101** according to one embodiment. The active region **105** may have a structure extending upwardly. The active region **105** may be formed as a portion of the substrate **101**, or may include an epitaxial layer grown from the substrate **101**. However, on both sides of the gate structure GS, the active region **105** may be partially recessed to form recess regions, and source/drain regions **150** may be disposed in the recess regions.

(21) In example embodiments, the active region **105** may or may not include a well region including impurities. For example, in the case of a P-type transistor (pFET), the well region may include N-type impurities such as phosphorus (P), arsenic (As), or antimony (Sb), and in the case of an N-type transistor, the well region may include P-type impurities such as boron (B), gallium (Ga), or aluminum (Al). In the case of including the well region, the well region may be located at a predetermined depth from the upper surface of the active region **105**.

(22) The device isolation layer **110** may define the active region **105** in the substrate **101**. The device isolation layer **110** may be formed by, for example, a shallow trench isolation (STI) process. In some embodiments, the device isolation layer **110** may further include a region extending relatively further deeply while having a step into a lower portion of the substrate **101**. The device isolation layer **110** may expose an upper surface of the active region **105**, or partially expose an upper portion of the active region **105**. In example embodiments, the device isolation layer **110** may have a curved upper surface to have a higher level as it approaches the active region **105**. In some embodiments, "level" may mean a height level when viewed with respect to a reference plane, such as an upper surface of the substrate **101**. When an Element A is said to be at a "higher

level” than Element B, this may mean that Element A is a height level that is further away from an upper surface of the substrate **101** than the height level of Element B. When an Element A is said to be at a “lower level” than Element B, this may mean that Element A is a height level that is closer to an upper surface of the substrate **101** than the height level of Element B. The device isolation layer **110** may be formed of an insulating material. The device isolation layer **110** may be formed of, for example, an oxide, a nitride, or a combination thereof.

(23) The channel structure **140** may be on the active region **105** in regions in which the active region **105** intersects the gate structure GS. The channel structure **140** may include first to third channel layers **141**, **142**, and **143**, which are two or more channel layers spaced apart from each other in the Z-direction. The channel structure **140** may be connected to the source/drain regions **150**, such as by being electrically connected. The channel structure **140** may have a width equal to or smaller than that of the active region **105** in the Y-direction, and may have a width equal to or similar to that of the gate structure GS in the X-direction. In some embodiments, the channel structure **140** may have a reduced width such that side surfaces are below the gate structure GS in the X-direction. As used herein, when the term Element A is “below” Element B is used, it may refer to the situation where Element A is closer to a reference plane, such as substrate **101**, in a particular direction than Element B. Likewise, when the term Element A is “above” Element B is used, it may refer to the situation where Element A is further away from a reference plane, such as substrate **101**, in a particular direction than Element B.

(24) The channel structure **140** may be formed of a semiconductor material, and may include, for example, at least one of silicon (Si), silicon germanium (SiGe), and germanium (Ge). The channel structure **140** may be formed of, for example, the same material as a material of the substrate **101**. In some embodiments, the channel structure **140** may include an impurity region in a region adjacent to the source/drain regions **150**. The number and shape of the channel layers constituting one channel structure **140** may be variously changed in the example embodiments. For example, in some embodiments, the channel structure **140** may further include a channel layer below a lowermost portion of the gate electrode **170**.

(25) The source/drain regions **150** may be on both sides of the gate structure GS in recess regions partially recessed from the upper portions of the active regions **105**, such that at least one source/drain region **150** is on each side of the gate structure GS. The source/drain regions **150** may be on, and at least partially cover, side surfaces of each of the first to third channel layers **141**, **142**, and **143** of the channel structure **140**. The upper surfaces of the source/drain regions **150** may be at the same or similar height as the lower surface of an uppermost portion of the gate electrode **170**, and the height may be variously changed in example embodiments. According to example embodiments, the source/drain regions **150** may be connected to or merged with each other on two or more active regions **105** adjacent to each other in the Y-direction to form one source/drain region **150**. The source/drain regions **150** may include impurities.

(26) The gate structure GS may intersect the active region **105** and the channel structure **140** to extend in the second direction, for example, the Y-direction. Channel regions of transistors may be formed in the channel structure **140** intersecting the gate electrode **170** of the gate structure GS. The gate structure GS may include the gate electrode **170**, the gate dielectric layers **162** between the gate electrode **170** and the channel structure **140**, and the gate spacer layers **164** on sides of the gate electrode **170**. In some embodiments, the gate structure GS may further include a capping layer on the upper surface of the gate electrode **170**. Alternatively, a portion of the interlayer insulating layer **190** on the gate structure GS may be referred to as a gate capping layer.

(27) The gate dielectric layers **162** may be between the active region **105** and the gate electrode **170** and between the channel structure **140** and the gate electrode **170**, and may be on, and cover at least a portion of, the surfaces of the gate electrode **170**. For example, the gate dielectric layers **162** may surround all surfaces except an uppermost surface of the gate electrode **170**. The gate dielectric layers **162** may extend between the gate electrode **170** and the gate spacer layers **164**, but the

configuration is not limited thereto. The gate dielectric layers **162** may include oxide, nitride, or a high-k material. The high-k material may refer to a dielectric material having a higher dielectric constant than that of a silicon oxide layer (SiO.sub.2). The high-k material may be any one of, for example, aluminum oxide (Al.sub.2O.sub.3), tantalum oxide (Ta.sub.2O.sub.3), titanium oxide (TiO.sub.2), yttrium oxide (Y.sub.2O.sub.3), zirconium oxide (ZrO.sub.2), zirconium silicon oxide (ZrSi.sub.xO.sub.y), hafnium oxide (HfO.sub.2), hafnium silicon oxide (HfSi.sub.xO.sub.y), lanthanum oxide (La.sub.2O.sub.3), lanthanum aluminum oxide (LaAl.sub.xO.sub.y), lanthanum hafnium oxide (LaHf.sub.xO.sub.y), hafnium aluminum oxide (HfAl.sub.xO.sub.y), and praseodymium oxide (Pr.sub.2O.sub.3). In some embodiments, the gate dielectric layers **162** may be formed of a multilayer film.

(28) The gate spacer layers **164** may be on both sides of the gate electrode **170**. The gate spacer layers **164** may insulate the source/drain regions **150** from the gate electrode **170**. In some embodiments, the gate spacer layers **164** may have a multi-layer structure. The gate spacer layers **164** may be formed of oxide, nitride, and oxynitride, and in detail, a low-k film, wherein a low-k film may refer to a dielectric material having the same dielectric constant as that of a silicon oxide layer (SiO.sub.2) or having a lower dielectric constant than that of a silicon oxide layer (SiO.sub.2).

(29) The gate electrode **170** may be on the active region **105** to at least partially fill a gap between the channel structures **140** and extend upwardly from the channel structures **140**. The gate electrode **170** may be spaced apart from the channel structure **140** by the gate dielectric layers **162**. The gate electrode **170** may include first to third electrode layers **172**, **174**, and **176** sequentially stacked from the gate dielectric layers **162**. The first electrode layer **172** may comprises a plurality of layers in some embodiments and may be a single layer in other embodiments. The term “first electrode layer **172**” as used herein may refer to a single layer or a plurality of layers but will include at least one layer.

(30) As illustrated in FIGS. 2B and 3, in a cross-section of the gate electrode **170**, the first electrode layer **172** may surround the first to third channel layers **141**, **142**, and **143** respectively, and may be spaced apart from each other in the Z-direction. It will be understood that “an element A surrounds an element B” (or similar language) as used herein means that the element A is at least partially around the element B but does not necessarily mean that the element A completely encloses the element B, unless it is so indicated. The first electrode layer **172** may further be on upper surfaces of the active region **105** and the device isolation layer **110**. A gate dielectric layer **162** may be between the first electrode layer **172** and the first to third channel layers **141**, **142**, and **143** and between the first electrode layer **172** and the active region **105**. In this embodiment, the first electrode layer **172** may have a uniform or constant thickness. The first electrode layer **172** may be spaced apart from the air gap regions AG and may not contact the air gap regions AG.

(31) The second electrode layer **174** may be on the first electrode layer **172**. The second electrode layer **174** may be between the first to third channel layers **141**, **142**, and **143** together with the first electrode layer **172**. As illustrated in FIGS. 2B and 3, the second electrode layer **174** may surround the respective first to third channel layers **141**, **142**, and **143** in a cross-section of the gate electrode **170**, and may be in a connected form in the Z-direction as a single layer. The second electrode layer **174** may extend downwardly along side surfaces of the first to third channel layers **141**, **142** and **143**, and may have a curve corresponding to side surfaces of the first to third channel layers **141**, **142** and **143**. Air gap regions AG are in the second electrode layer **174**, and the second electrode layer **174** may completely or entirely surround the respective air gap regions AG in some embodiments.

(32) The second electrode layer **174** may have a non-uniform or non-constant thickness and may be non-conformally disposed around the first to third channel layers **141**, **142**, and **143**. The second electrode layer **174** may be on the upper surface of the active region **105**, on portions of the upper surfaces of the first to third channel layers **141**, **142**, and **143**, and on lower surfaces of the first to third channel layers **141**, **142** and **143**, and may have a relatively thin thickness or reduced

thickness. The second electrode layer **174** may have a relatively thin thickness between the first to third channel layers **141**, **142**, and **143** and between the first channel layer **141** and the active region **105**. The second electrode layer **174** may have a relatively thin thickness above and below the air gap regions AG. As illustrated in FIG. 3, the second electrode layer **174** may have a first thickness **T1** in a region extending horizontally toward the air gap regions AG, and may have a second thickness **T2** greater than the first thickness **T1** on the side surfaces of the first to third channel layers **141**, **142** and **143** and the upper surface of the device isolation layer **110**. The second electrode layer **174** may have the first thickness **T1** in a region overlapping the air gap regions AG in the Z-direction. As used herein, when element A is said to “overlap” or is “overlapping” element B, it may refer to the situation where element A is said to extend over or past, and cover a part of, element B in a given direction. Note that element A may overlap element B in a first direction, but may or may not overlap element B in a second direction. The second electrode layer **174** may be formed by a method different from that of the first electrode layer **172**, to have the profile as described above. This will be described in more detail below with reference to FIGS. 9 and 10G.

(33) The third electrode layer **176** may be on the second electrode layer **174** and may extend in the Y-direction while filling between the adjacent active regions **105**. Unlike the first and second electrode layers **172** and **174**, the third electrode layer **176** may not be between the first to third channel layers **141**, **142**, and **143** in the Z-direction. The third electrode layer **176** may have a thickness greater than that of the first and second electrode layers **172** and **174**. In some embodiments, the third electrode layer **176** may be omitted.

(34) The gate electrode **170** may include a conductive material, for example, a metal nitride such as titanium nitride (TiN), tantalum nitride (TaN), or tungsten nitride (WN), and/or a metal material such as aluminum (Al), tungsten (W), or molybdenum (Mo), or a semiconductor material such as doped polysilicon. The first to third electrode layers **172**, **174**, and **176** may include different materials. The first electrode layer **172** and the second electrode layer **174** may include materials having different work functions. For example, the second electrode layer **174** may include a material having a lower work function than a work function of the first electrode layer **172**. For example, the first electrode layer **172** may include Titanium Nitride (TiN), the second electrode layer **174** may include aluminum (Al), for example, Titanium Aluminum Carbide (TiAlC) or Titanium Aluminum Nitride (TiAlN), and the third electrode layer **176** may include tungsten (W) or molybdenum (Mo).

(35) The air gap regions AG may be between the first to third channel layers **141**, **142**, and **143** and between the first channel layer **141**, which is the lowermost channel layer of the first to third channel layers **141**, **142**, **143**, and the active region **105**. The air gap regions AG may be located in the second electrode layer **174**, and thus may be defined by the second electrode layer **174**. The air gap regions AG are regions formed of air or gas, but in the present specification, for ease of understanding, may be regarded as one region or layer. A plurality of air gap regions AG may be spaced apart from each other in the Z-direction. The number of air gap regions AG may be changed according to the number of channel layers constituting the channel structure **140**.

(36) Lengths of the air gap regions AG in a horizontal direction, for example, an X-direction and a Y-direction, may be relatively longer than lengths in a vertical direction, for example, a Z-direction. The length of the air gap regions AG in the vertical direction may be determined by the distance between the first to third channel layers **141**, **142**, and **143** (a separation distance) and the thickness of the first and second electrode layers **172** and **174**. By adjusting at least one of a uniform thickness of the first electrode layer **172** and a non-uniform thickness of the second electrode layer **174**, the size of the air gap regions AG may be adjusted, and accordingly, the threshold voltage of the semiconductor device **100** may be adjusted. For example, the length of the air gap regions AG in the vertical direction may be in the range of about 20% to about 50% of the distance between the adjacent channel layers **141**, **142**, and **143**. For example, the length may range from about one nanometer (1 nm) to about five (5) nm, but is not limited thereto.

(37) The inner spacer layers **130** may be between the channel structures **140** in parallel with the gate electrode **170**. The gate electrode **170** may be stably spaced apart from the source/drain regions **150** by the inner spacer layers **130** to be electrically isolated from each other. The inner spacer layers **130** may have a shape in which the side surface facing the gate electrode **170** is inwardly, convexly rounded toward the gate electrode **170**, but the configuration is not limited thereto. The inner spacer layers **130** may be formed of oxide, nitride, or oxynitride, and in detail, may be formed of a low-k film. However, in some embodiments, the inner spacer layers **130** may be omitted.

(38) The contact plugs **180** may pass through the interlayer insulating layer **190** to be connected to the source/drain regions **150**, and may apply an electrical signal to the source/drain regions **150**. The contact plugs **180** may have inclined side surfaces in which a lower width is narrower than an upper width according to an aspect ratio, but the configuration is not limited thereto. For example, the contact plugs **180** may extend downwardly from an upper portion, for example, to further below the lower surface of the third channel layer **143**, but the configuration is not limited thereto. In some example embodiments, the contact plugs **180** may contact upper surfaces of the source/drain regions **150** without recessing the source/drain regions **150**.

(39) The contact plugs **180** may include a metal silicide layer on a lower end including a lower surface, and may further include a barrier layer on an upper surface and sidewalls of the metal silicide layer. The barrier layer may include, for example, a metal nitride such as titanium nitride (TiN), tantalum nitride (TaN), or tungsten nitride (WN). The contact plugs **180** may include, for example, a metal material such as aluminum (Al), tungsten (W), or molybdenum (Mo). In example embodiments, the number and arrangement of the conductive layers constituting the contact plugs **180** may be variously changed.

(40) The interlayer insulating layer **190** may be on, and at least partially cover, the source/drain regions **150** and the gate structure GS, and be on, and at least partially cover, the device isolation layer **110**. The interlayer insulating layer **190** may include at least one of an oxide, a nitride, and an oxynitride, and may include, for example, a low-k material. In some embodiments, the interlayer insulating layer **190** may include a plurality of insulating layers.

(41) FIGS. **4A** and **4B** are schematic cross-sectional views and partially enlarged views illustrating a semiconductor device according to an example embodiment. FIG. **4B** illustrates an enlarged area 'B' of FIG. **4A**. FIGS. **4A** and **4B** may include elements similar to those previously discussed. Thus, the same or similar reference numerals may be used to refer to the same or similar elements, and a description of those elements will not be repeated here.

(42) Referring to FIGS. **4A** and **4B**, in a semiconductor device **100a**, the shapes of first and second electrode layers **172a** and **174a** of a gate electrode layer **170a** may be different from those of the example embodiments of FIGS. **2** and **3**.

(43) The first electrode layer **172a** may have a non-uniform or non-constant thickness around the first to third channel layers **141**, **142**, and **143** and may be non-conformally disposed thereon. The first electrode layer **172a** have a relatively thin first thickness **T1'** between the first to third channel layers **141**, **142** and **143** and on the upper surface of the active region **105**, and may have a second thickness **T2'** greater than the first thickness **T1'** on side surfaces of the first to third channel layers **141**, **142**, and **143**. The first electrode layer **172a** may have a relatively thin thickness in a region overlapping the air gap regions AGa in the Z-direction. In contrast, the second electrode layer **174a** may have a uniform or constant thickness on the first electrode layer **172a**.

(44) In some embodiments, according to the profiles of the first electrode layer **172a** and the second electrode layer **174a**, air gap regions AGa may have a relatively thinned shape on the ends as compared to on the central portions in a cross-section in the Y-direction. However, the detailed shape of the air gap regions AGa is not limited thereto.

(45) In some embodiments, a fourth electrode layer (not shown) may be between the gate dielectric layers **162** and the first electrode layer **172a**. In this case, the fourth electrode layer may be a layer

having a constant thickness similar to that of the second electrode layer **174a**, and may be formed in a process different from that of the first electrode layer **172a**, and may be formed in the same process as the second electrode layer **174a**.

(46) FIG. 5 includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments. FIG. 5 may include elements similar to those previously discussed. Thus, the same or similar reference numerals may be used to refer to the same or similar elements, and a description of those elements will not be repeated here.

(47) Referring to FIG. 5, in a semiconductor device **100b**, a gate electrode layer **170b** may not include a layer corresponding to the first electrode layer **172** in the example embodiment of FIGS. 2 and 3. The gate electrode layer **170b** may include a second electrode layer **174** and a third electrode layer **176**. The second electrode layer **174** may be on gate dielectric layers **162**, and as described above with reference to FIGS. 1 to 3, may have a reduced thickness between the first to third channel layers **141**, **142**, and **143** and on the upper surface of the active region **105**.

(48) FIGS. 6A and 6B are a layout view and a schematic cross-sectional view illustrating a semiconductor device according to example embodiments, respectively. FIG. 6B illustrates cross-sections taken along lines III-III', IV-IV', and V-V' of FIG. 6A.

(49) Referring to FIGS. 6A and 6B, in a semiconductor device **100c**, a substrate **101** may have first to third regions **R1**, **R2**, and **R3**. The first to third regions **R1**, **R2** and **R3** may be areas adjacent to or spaced apart from each other, and may be areas in which first to third gate electrodes **170A**, **170B**, and **170C**, each including respective first electrode layers **172** with different thicknesses, are disposed respectively.

(50) First to third transistors including the first to third gate electrodes **170A**, **170B**, and **170C**, respectively, may be transistors driven under different threshold voltages, and may constitute the same circuit or different circuits in the semiconductor device **100c**. For example, when the first to third transistors are pFETs, a first transistor of the first region **R1** may have a lowest threshold voltage and operating voltage, based on the absolute value, and a third region of the third transistor **R3** may have a highest threshold voltage and operating voltage.

(51) In each of the first to third regions **R1**, **R2**, and **R3**, each of the first electrode layers **172** may have a substantially uniform thickness. On the first region **R1**, the first electrode layer **172** has a third thickness **T3**, and on the second region **R2**, the first electrode layer **172** have a fourth thickness **T4** less than a third thickness **T3**, and on the third region **R3**, the first electrode layer **172** may have a fifth thickness **T5** less than the fourth thickness **T4**. The thicknesses may be, for example, an average thickness or thicknesses on corresponding locations. For example, the first electrode layer **172** of the first region **R1** may be formed by depositing a preliminary first electrode layer three times, the first electrode layer **172** of the second region **R2** may be formed by depositing the preliminary first electrode layer twice, and the first electrode layer **172** of the third region **R3** may be formed by depositing the preliminary first electrode layer once. This structure of the first electrode layer **172** may be formed by the patterning that uses a protective layer deposited to a relatively thin thickness, between the first to third channel layers **141**, **142** and **143**, to have a form similar to that of the second electrode layers **174**. This will be described in more detail below with reference to FIGS. 11A to 11G.

(52) In the first region **R1**, air gap regions **AG** may not be located in the first gate electrode **170A**. Accordingly, the first electrode layer **172** may be vertically connected to form one layer, and a space between the first to third channel layers **141**, **142**, and **143** may be at least partially filled with the first electrode layer **172**. In the second and third regions **R2** and **R3**, the air gap regions **AG** may be located in the second and third gate electrodes **170B** and **170C**, as described with reference to FIGS. 1 to 3.

(53) The second electrode layer **174** may have the same average thickness in the first to third regions **R1**, **R2**, and **R3**, but the configuration is not limited thereto. In the first region **R1**, the second electrode layer **174** may extend toward the substrate **101** along the first electrode layer **172**.

As for the description of the second electrode layer **174** in the second and third regions **R2** and **R3**, the description with reference to FIGS. **1** to **3** may be equally applied. In the example embodiments, since the thicknesses of the first electrode layer **172** are different from each other, when the thicknesses of the second electrode layers **174** are equal to each other, a height **L1** in the Z-direction of the air gap regions **AG** in the second region **R2** may be less than a height **L2** in the Z-direction of the air gap regions **AG** in the third region **R3**. In some embodiments, the semiconductor device **100c** may include only two of the first to third regions **R1**, **R2**, and **R3**.

(54) FIG. **7** includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments. FIG. **7** may include elements similar to those previously discussed. Thus, the same or similar reference numerals may be used to refer to the same or similar elements, and a description of those elements will not be repeated here.

(55) Referring to FIG. **7**, in a semiconductor device **100d**, unlike the example embodiment of FIG. **6B**, air gap regions **AG** may be located in a first gate electrode **170A** in the first region **R1**. Also in this embodiment, the first electrode layer **172** on the first region **R1** may have a third thickness **T3d**, the first electrode layer **172** on the second region **R2** may have a fourth thickness **T4d** less than the third thickness **T3d**, and the first electrode layer **172** on the third region **R3** may have a fifth thickness **T5d** that is less than the fourth thickness **T4d**. In some embodiments, the semiconductor device **100d** may include only two of the first to third regions **R1**, **R2**, and **R3**.

(56) As such, in example embodiments, the presence or absence of the air gap regions **AG** according to the region may be changed depending on a separation distance between the first to third channel layers **141**, **142**, and **143** and a relative thickness of the first electrode layer **172**.

(57) FIG. **8** includes schematic cross-sectional views illustrating a semiconductor device according to example embodiments. FIG. **8** may include elements similar to those previously discussed. Thus, the same or similar reference numerals may be used to refer to the same or similar elements, and a description of those elements will not be repeated here.

(58) Referring to FIG. **8**, a semiconductor device **100e** may not include the inner spacer layer **130**, unlike the example embodiment of FIGS. **2** and **3**. In this case, the source/drain regions **150** may expand to regions in which the inner spacer layers **130** are omitted, to have an expanded shape. The gate electrode **170** may be spaced apart from the source/drain regions **150** by the gate dielectric layers **162**. In another embodiment, the source/drain regions **150** may not expand to the region in which the inner spacer layers **130** are omitted, but the gate electrode **170** may expand in the X-direction.

(59) According to this structure, when the inner spacer layer **130** is omitted and the source/drain regions **150** are grown, the source/drain regions **150** may have improved crystallinity. In some embodiments, the inner spacer layer **130** may be omitted only in some devices of the semiconductor device **100e**. For example, when SiGe is used for the source/drain regions **150** in a pFET, the inner spacer layer **130** may be selectively omitted only in the pFET to improve the crystallinity of SiGe.

(60) FIG. **9** is a flowchart illustrating a method of manufacturing a semiconductor device according to example embodiments.

(61) FIGS. **10A** to **10H** are views illustrating a process sequence to illustrate a method of manufacturing a semiconductor device according to example embodiments. An example embodiment of a method of manufacturing the semiconductor device of FIGS. **1** to **3** is described with reference to FIGS. **10A** to **10H**.

(62) Referring to FIGS. **9** and **10A**, sacrificial layers **120** and first to third channel layers **141**, **142**, and **143** may be alternately stacked on a substrate **101** (**S110**).

(63) The sacrificial layers **120** may be the layers replaced by the gate dielectric layers **162** and the gate electrode **170** as illustrated in FIG. **2** through a subsequent process. The sacrificial layers **120** may be formed of a material respectively having etch selectivity with respect to the first to third channel layers **141**, **142**, and **143**. The first to third channel layers **141**, **142**, and **143** may include a

material different from that of the sacrificial layers **120**. The sacrificial layers **120** and the first to third channel layers **141**, **142**, and **143** may include a semiconductor material including at least one of silicon (Si), silicon germanium (SiGe), and germanium (Ge), but may include different materials, and may or may not contain impurities. For example, the sacrificial layers **120** may include silicon germanium (SiGe), and the first to third channel layers **141**, **142**, and **143** may include silicon (Si).

(64) The sacrificial layers **120** and the first to third channel layers **141**, **142**, and **143** may be formed by performing an epitaxial growth process from the substrate **101**. Each of the sacrificial layers **120** and the first to third channel layers **141**, **142**, and **143** may have a thickness in a range of about one Angstrom (1 Å) to about one hundred (100) nm. The number of layers of the channel layers **141**, **142**, and **143** alternately stacked with the sacrificial layers **120** may be variously changed in example embodiments.

(65) Referring to FIGS. **9** and **10B**, an active structure may be formed by removing portions of the sacrificial layers **120**, the first to third channel layers **141**, **142** and **143**, and the substrate **101**, and the device isolation layer **110** may be formed (**S120**).

(66) The active structure may include the sacrificial layers **120** and the first to third channel layers **141**, **142**, and **143** stacked alternately with each other, and may further include the active region **105** that is formed to extend from the substrate **101** by removing a portion of the substrate **101**. The active structure may be formed in the form of a line extending in one direction, for example, the X-direction, and the active structures may be formed to be spaced apart from each other in the Y-direction.

(67) In the region from which a portion of the substrate **101** has been removed, the insulating material is partially or completely filled, and then, the insulating material is partially removed such that the active region **105** protrudes, thereby forming the device isolation layer **110**. The upper surface of the device isolation layer **110** may be formed to be lower than the upper surface of the active region **105**.

(68) Referring to FIGS. **9** and **10C**, a sacrificial gate structure SS and gate spacer layers **164** may be formed on the active structure (**S130**).

(69) The sacrificial gate structure SS may be a sacrificial structure formed in a region in which the gate dielectric layers **162** and the gate electrode **170** are disposed, on the channel structure **140** through a subsequent process, as illustrated in FIG. **2**. The sacrificial gate structure SS may include first and second sacrificial gate layers **202** and **204** and a mask pattern layer **206** that are sequentially stacked. The first and second sacrificial gate layers **202** and **204** may be patterned using a mask pattern layer **206**. The first and second sacrificial gate layers **202** and **204** may be an insulating layer and a conductive layer, respectively, but are not limited thereto, and the first and second sacrificial gate layers **202** and **204** may also be formed as a single layer. For example, the first sacrificial gate layer **202** may include silicon oxide, and the second sacrificial gate layer **205** may include polysilicon. The mask pattern layer **206** may include silicon oxide and/or silicon nitride. The sacrificial gate structure SS may have a line shape that intersects the active structures and extends in one direction. The sacrificial gate structure SS may extend in, for example, a Y-direction, and may be spaced apart from a sacrificial gate structure SS adjacent thereto in the X-direction.

(70) The gate spacer layers **164** may be formed on both sidewalls of the sacrificial gate structure SS. The gate spacer layers **164** may be formed of a low-k material, and may include, for example, at least one of SiO, SiN, SiCN, SiOC, SiON, and SiOCN.

(71) Referring to FIGS. **9** and **10D**, on the outside of the sacrificial gate structure SS, the exposed sacrificial layers **120** and first to third channel layers **141**, **142**, and **143** may be partially removed to form recess regions, inner spacer layers **130** may be formed, and source/drain regions **150** partially or completely filling the recess regions may be formed (**S140**).

(72) First, the exposed sacrificial layers **120** and first to third channel layers **141**, **142**, and **143** are

removed using the sacrificial gate structure SS and the gate spacer layers **164** as masks, thereby forming recess regions. Accordingly, the first to third channel layers **141**, **142**, and **143** may form the channel structure **140** having a limited length in the X-direction.

(73) Next, portions of the sacrificial layers **120** may be removed. The sacrificial layers **120** may be selectively etched with respect to the channel structure **140** by, for example, a wet etching process, and may be removed to a predetermined depth from the side surface in the X-direction. The sacrificial layers **120** may have inwardly concave side surfaces by side etching as described above. However, the shape of the side surfaces of the sacrificial layers **120** is not limited to the illustration.

(74) Next, the inner spacer layers **130** may be formed in the regions from which the sacrificial layers **120** have been partially removed. The inner spacer layers **130** may be formed of the same material as the gate spacer layers **164**, but the material is not limited thereto. For example, the inner spacer layers **130** may include at least one of SiN, SiCN, SiOCN, SiBCN, and SiBN.

(75) Next, the source/drain regions **150** may be formed by growing from the upper surface of the active region **105** and side surfaces of the channel structure **140**, for example, by a selective epitaxial process. The source/drain regions **150** may include impurities by in-situ doping, and may also include a plurality of layers having different doping elements and/or doping concentrations.

(76) Referring to FIGS. **9** and **10E**, after the interlayer insulating layer **190** is formed, the sacrificial layers **120** and the sacrificial gate structure SS may be removed (S150).

(77) The interlayer insulating layer **190** may be formed by forming an insulating layer at least partially covering the sacrificial gate structure SS and the source/drain regions **150** and performing a planarization process.

(78) The sacrificial layers **120** and the sacrificial gate structure SS may be selectively removed with respect to the gate spacer layers **164**, the interlayer insulating layer **190**, and the channel structure **140**. First, the sacrificial gate structure SS is removed to form an upper gap region UR, and lower gap regions LR may be formed by removing the sacrificial layers **120** exposed through the upper gap region UR. For example, when the sacrificial layers **120** include silicon germanium (SiGe) and the channel structures **140** include silicon (Si), the sacrificial layers **120** may be selectively removed by performing a wet etching process using peracetic acid as an etchant. During the removal process, the source/drain regions **150** may be protected by the interlayer insulating layer **190** and the inner spacer layers **130**.

(79) Hereinafter, operation (S160) of forming the gate structure **160** will be described with reference to FIGS. **9** and **10F** to **10H**.

(80) First, referring to FIGS. **9** and **10F**, the gate dielectric layers **162** may be formed (S162), and the first electrode layer **172** may be formed to have a uniform thickness (S164).

(81) The gate dielectric layers **162** may be formed to conform to, and at least partially cover, inner surfaces of the upper gap region UR and the lower gap regions LR.

(82) The first electrode layer **172** may be formed to conform to, and at least partially cover, the gate dielectric layers **162** in the upper gap region UR and the lower gap regions LR. For example, the first electrode layer **172** may be formed to have a uniform thickness using thermal atomic layer deposition. The first electrode layer **172** may be formed to have a substantially uniform thickness on a circumference of the channel structure **140**. The size of air gap regions AG (refer to FIG. **10G**) to be formed subsequently may be adjusted by the thickness of the first electrode layer **172**.

(83) Referring to FIGS. **9** and **10G**, the second electrode layer **174** may be formed to have a non-uniform thickness (S166).

(84) The second electrode layer **174** may surround the first electrode layer **172** in the upper gap region UR and the lower gap regions LR and extend onto the active region **105** and the device isolation layer **110**. The second electrode layer **174** may be formed to completely fill the lower gap regions LR in some embodiments.

(85) The second electrode layer **174** may be formed by using a different deposition process from that of the first electrode layer **172**. For example, the second electrode layer **174** may be formed to

have a non-uniform thickness using a plasma-enhanced atomic layer deposition (PEALD) method. This may be because, in the PEALD process, the deposition material is directionally supplied and deposited by plasma. The second electrode layer **174** is formed to be relatively thin in a region extending horizontally between the channel structures **140** and between the first channel layer **141** and the active region **105**, and to be relatively thick in other regions.

(86) Between the first to third channel layers **141**, **142** and **143** and between the first channel layer **141** and the active region **105**, the second electrode layer **174** may be deposited to a thickness that does not fill the spaces between the first to third channel layers **141**, **142**, and **143**. Accordingly, the air gap regions AG may be formed between the first to third channel layers **141**, **142**, and **143** and between the first channel layer **141** and the active region **105**. The size of the air gap regions AG may also be adjusted by the thickness of the second electrode layer **174**. In example embodiments, the relative thicknesses of the first electrode layer **172** and the second electrode layer **174** may be variously changed.

(87) In the case of the example embodiment of FIGS. **4A** and **4B**, in contrast to the present embodiment, the first electrode layer **172a** may be formed by PEALD, and then the second electrode layer **174a** may be formed by thermal ALD.

(88) Referring to FIGS. **9** and **10H**, a third electrode layer **176** may be formed (**S168**).

(89) The third electrode layer **176** may be formed on the second electrode layer **174** in the upper gap region UR, and may be formed to completely fill the upper gap region UR in some embodiments. Accordingly, the gate structure GS may be formed. The third electrode layer **176** may be formed to have a substantially flat upper surface by a planarization process or the like. In some embodiments, the third electrode layer **176** may include a plurality of conductive layers.

(90) Next, an interlayer insulating layer **190** may be further formed on the gate structure GS.

(91) Next, referring to FIG. **2**, contact plugs **180** may be formed (**S170**).

(92) First, the interlayer insulating layer **190** may be patterned to form contact holes exposing the source/drain regions **150**. Contact plugs **180** may be formed by partially or completely filling the contact holes with a conductive material. In detail, after depositing a material forming a barrier layer in the contact holes, a silicide process may be performed to form a metal-semiconductor compound layer such as a silicide layer on a lower end. Next, a conductive material may be deposited to partially or completely fill the contact holes to form the contact plugs **180**.

Accordingly, the semiconductor device **100** of FIGS. **1** to **3** may be manufactured.

(93) FIGS. **11A** to **11G** are diagrams illustrating a process sequence to illustrate a method of manufacturing a semiconductor device according to example embodiments. An example embodiment of a method of manufacturing the semiconductor device of FIGS. **6A** and **6B** will be described with reference to FIGS. **11A** to **11G**. FIGS. **11A-11G** may include elements similar to those previously discussed. Thus, the same or similar reference numerals may be used to refer to the same or similar elements, and a description of those elements will not be repeated here.

(94) Referring to FIG. **11A**, in the first to third regions R1, R2 and R3, the operations described above with reference to FIGS. **10A** to **10E** are performed in the same manner, and after forming the upper gap region UR and the lower gap regions LR, preliminary first electrode layer **172P** may be formed.

(95) The preliminary first electrode layer **172P** may be formed to conform to, and at least partially cover, the gate dielectric layers **162** in the upper gap region UR and the lower gap regions LR in the first to third regions R1, R2, and R3. In this operation, the preliminary first electrode layer **172P** may be formed to have a fifth thickness T5. In the following embodiments of the manufacturing method, a case in which a ratio (T3:T4:T5) of the third thickness (T3), the fourth thickness (T4), and the fifth thickness (T5) of FIG. **6B** is 3:2:1 will be described. However, the ratio (T3:T4:T5) is not limited thereto.

(96) Referring to FIG. **11B**, a first protective layer PL1 may be formed in the first to third regions R1, R2, and R3, and a first mask layer ML1 may be formed in the first region R1.

(97) The first protective layer PL1 may be nonconformally formed, while surrounding the preliminary first electrode layer 172P. The first protective layer PL1 may include, for example, at least one of aluminum oxide (AlOx), titanium oxide (TiOx), and titanium nitride (TiN). The first protective layer PL1 may be formed in the same manner as the second electrode layer 174 described above with reference to FIG. 10G. For example, the first protective layer PL1 may be formed to have a non-uniform thickness using PEALD. The first protective layer PL1 is formed to be relatively thin in a region extending horizontally between the channel structures 140 and between the first channel layer 141 and the active region 105, and may be formed to be relatively thick in other regions. Accordingly, between the first to third channel layers 141, 142 and 143 and between the first channel layer 141 and the active region 105, air gap regions AG' may be formed in the first protective layer PL1.

(98) The first mask layer ML1 may be formed to at least partially cover the first region R1. The first mask layer ML1 may be, for example, a photoresist layer, but is not limited thereto.

(99) Referring to FIG. 11C, the first protective layer PL1 and the preliminary first electrode layer 172P may be removed from the second and third regions R2 and R3.

(100) The first protective layer PL1 may be removed from the second and third regions R2 and R3 exposed from the first mask layer ML1, thereby removing the exposed preliminary first electrode layer 172P. Accordingly, the preliminary first electrode layer 172P may remain only in the first region R1.

(101) In this operation, since the air gap regions AG' are formed in the first protective layer PL1, the path of the etchant is secured, and a defect in which the first protective layer PL1 remains between the first to third channel layers 141, 142, and 143 and between the first channel layer 141 and the active region 105 may be prevented.

(102) Referring to FIG. 11D, the first mask layer ML1 and the first protective layer PL1 may be removed from the first region R1, and preliminary first electrode layer 172P may be additionally formed in the first to third regions R1, R2, and R3.

(103) First, the first mask layer ML1 and the first protective layer PL1 may be sequentially removed from the first region R1 to expose the preliminary first electrode layer 172P. In this operation, since the air gap regions AG' are formed in the first protective layer PL1, the path of the etchant is secured, and thus, defects in which the first protective layer PL1 remains between the first to third channel layers 141, 142, and 143 and between the first channel layer 141 and the active region 105, or in which lower preliminary first electrode layers 172P are damaged, may be prevented.

(104) Next, preliminary first electrode layer 172P may be additionally formed in the entire first to third regions R1, R2, and R3. In this operation, the preliminary first electrode layer 172P may be further formed with a fifth thickness T5. Accordingly, in the first region R1, the preliminary first electrode layer 172P have a fourth thickness T4 that is twice the fifth thickness T5, and in the second and third regions R2 and R3, the preliminary first electrode layer 172P may have the fifth thickness T5.

(105) Referring to FIG. 11E, a second protective layer PL2 may be formed in the first to third regions R1, R2 and R3, and a second mask layer ML2 may be formed in the first and second regions R1 and R2.

(106) The second mask layer ML2 may be formed to expose the third region R3. The second protective layer PL2 and the second mask layer ML2 may be formed in the same manner as the first protective layer PL1 and the first mask layer ML1 described above with reference to FIG. 11B, respectively.

(107) Referring to FIG. 11F, the second protective layer PL2 and the preliminary first electrode layer 172P may be removed from the third region R3.

(108) The second protective layer PL2 may be removed from the third region R3 exposed from the second mask layer ML2, thereby removing the exposed preliminary first electrode layer 172P.

Accordingly, in the first region R1, the preliminary first electrode layer 172P have a fourth thickness T4, and in the second region R2, the preliminary first electrode layer 172P have a fifth thickness T5, and the preliminary first electrode layer 172P may not remain in the third region R3. (109) Referring to FIG. 11G, the second mask layer ML2 and the second protective layer PL2 are removed from the first and second regions R1 and R2, and the preliminary first electrode layer 172P may be additionally formed in the first to third regions R1, R2 and R3, thereby forming the first electrode layer 172.

(110) First, the second mask layer ML2 and the second protective layer PL2 are sequentially removed from the first and second regions R1 and R2, thereby exposing the preliminary first electrode layer 172P. Next, preliminary first electrode layer 172P may be additionally formed in the entire first to third regions R1, R2, and R3. In this operation, the preliminary first electrode layer 172P may be further formed with a fifth thickness T5. Accordingly, the preliminary first electrode layer 172P are stacked three times in the first region R1 to have a third thickness T3 that is three times the fifth thickness T5, and in the second region R2, the preliminary first electrode layer 172P are stacked twice to have a fourth thickness T4 that is twice the fifth thickness T5, and in the third region R3, the preliminary first electrode layer 172P may be formed once to have the fifth thickness T5.

(111) Next, the semiconductor device of FIGS. 6A and 6B may be manufactured by further performing the process described above with reference to FIGS. 10G and 10H. According to this manufacturing method, by forming the first electrode layer 172 to have different thicknesses in different areas, the formation of the MBCFET™ devices having various threshold voltages may be facilitated without defects.

(112) As set forth above, by including an air gap having a controlled size in the gate electrode, a semiconductor device having improved electrical characteristics and reliability may be provided.

(113) While example embodiments have been illustrated and described above, it will be apparent to those skilled in the art that modifications and variations could be made without departing from the scope of the present disclosure as defined by the appended claims.

Claims

1. A semiconductor device comprising: a substrate comprising an active region extending in a first direction; a gate electrode extending in a second direction and intersecting the active region on the substrate, the gate electrode comprising at least one first electrode layer and a second electrode layer; a plurality of channel layers on the active region and spaced apart from each other in a third direction perpendicular to an upper surface of the substrate, the plurality of channel layers at least partially surrounded by the gate electrode; a plurality of source/drain regions, with at least one source/drain region on each side of the gate electrode, the plurality of source/drain regions electrically connected to the plurality of channel layers; and one or more air gap regions in the second electrode layer between respective ones of the plurality of channel layers and between a lowermost channel layer of the plurality of channel layers and the active region in the third direction, wherein the at least one first electrode layer or the second electrode layer has a first thickness between adjacent ones of the plurality of channel layers in the third direction, and has a second thickness on side surfaces of the plurality of channel layers, and wherein the second thickness is greater than the first thickness.
2. The semiconductor device of claim 1, wherein a region in which the at least one first electrode layer or the second electrode layer has the first thickness comprises a region overlapping the one or more air gap regions in the third direction.
3. The semiconductor device of claim 1, wherein each of the one or more air gap regions is entirely surrounded by the second electrode layer.
4. The semiconductor device of claim 1, wherein the at least one first electrode layer comprises a

plurality of first electrode layers, and the plurality of first electrode layers at least partially surround the plurality of channel layers and are spaced apart from each other in the third direction, wherein the second electrode layer at least partially surrounds each of the plurality of channel layers and is in a connected form as a single layer in the third direction.

5. The semiconductor device of claim 4, wherein the second electrode layer extends along the side surfaces of the plurality of channel layers and has a curve corresponding to the side surfaces.

6. The semiconductor device of claim 1, wherein the gate electrode further comprises a third electrode layer on the second electrode layer and having a flat upper surface.

7. The semiconductor device of claim 1, wherein each of the one or more air gap regions has a length in a range of about 20% to about 50% of a distance between each of adjacent ones of the plurality of channel layers in the third direction.

8. The semiconductor device of claim 1, wherein the second electrode layer comprises a material having a work function different from a work function of the at least one first electrode layer.

9. The semiconductor device of claim 1, wherein the gate electrode comprises a first gate electrode and a second gate electrode spaced apart from each other, and wherein the at least one first electrode layer of the first gate electrode has a first average thickness, and the at least one first electrode layer of the second gate electrode has a second average thickness greater than the first average thickness.

10. A semiconductor device comprising: a substrate comprising an active region; a gate electrode extending on the substrate and intersecting the active region, the gate electrode comprising a first electrode layer; a plurality of channel layers on the active region and spaced apart from each other in a vertical direction perpendicular to an upper surface of the substrate, the plurality of channel layers at least partially surrounded by the gate electrode; a plurality of source/drain regions, with at least one source/drain region on each side of the gate electrode, the plurality of source/drain regions electrically connected to the plurality of channel layers; and one or more air gap regions in the gate electrode between the plurality of channel layers in the vertical direction, wherein the first electrode layer surrounds an entirety of each of the one or more air gap regions and has a reduced thickness in a region overlapping the one or more air gap regions in the vertical direction.

11. The semiconductor device of claim 10, wherein the first electrode layer has a first thickness between adjacent ones of the plurality of channel layers in the vertical direction, and has a second thickness greater than the first thickness on side surfaces of the plurality of channel layers.

12. The semiconductor device of claim 10, wherein the gate electrode further comprises a second electrode layer, and the first and second electrode layers comprise at least one different material from each other, and are both between adjacent ones of the plurality of channel layers in the vertical direction.

13. The semiconductor device of claim 10, wherein the gate electrode further comprises a second electrode layer between the plurality of channel layers and the first electrode layer, and the second electrode layer has a substantially constant thickness on a circumference of the plurality of channel layers.

14. The semiconductor device of claim 10, wherein the gate electrode further comprises a second electrode layer outside the first electrode layer, and the second electrode layer has a substantially constant thickness on a circumference of the plurality of channel layers.

15. The semiconductor device of claim 10, wherein the gate electrode further comprises a second electrode layer, wherein the first electrode layer has a non-uniform thickness and the second electrode layer has a uniform thickness, the first electrode layer has a first thickness between the plurality of channel layers and on an upper surface of the active region and in a region overlapping the one or more air gap regions in the vertical direction, and has a second thickness greater than the first thickness on side surfaces of the plurality of channel layers, and wherein the one or more air gap regions has a thinner shape on an end of the one or more air gap regions than on central portions of the one or more air gap regions in a direction perpendicular to the vertical direction.

