

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12386083
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Yamaji; Haruki et al.

Radiation detector, radiation detector manufacturing method, and scintillator panel unit

Abstract

A radiation detector includes a sensor panel having a light receiving surface, a first scintillator panel and a second scintillator panel disposed on the light receiving surface in a state of being adjacent to each other along the light receiving surface, and an adhesive layer. The first scintillator panel has a first substrate and a first scintillator layer including a plurality of columnar crystals. The second scintillator panel has a second substrate and a second scintillator layer including a plurality of columnar crystals. The first scintillator layer reaches at least a first portion of the first substrate. The second scintillator layer reaches at least a second portion of the second substrate. The adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

Inventors:	Yamaji; Haruki (Hamamatsu, JP), Sakurai; Jun (Hamamatsu, JP), Shirakawa; Kazuhiro (Hamamatsu, JP), Hatanaka; Masashi (Hamamatsu, JP), Goto; Keisuke (Hamamatsu, JP)
Applicant:	HAMAMATSU PHOTONICS K.K. (Hamamatsu, JP)
Family ID:	82157590
Assignee:	HAMAMATSU PHOTONICS K.K. (Hamamatsu, JP)
Appl. No.:	18/265493
Filed (or PCT Filed):	November 08, 2021
PCT No.:	PCT/JP2021/041000
PCT Pub. No.:	WO2022/137846
PCT Pub. Date:	June 30, 2022

Prior Publication Data

Foreign Application Priority Data

JP2020-213328Dec. 23, 2020

Publication Classification

Int. Cl.: G01T1/20 (20060101); H10F39/00 (20250101); H10F39/18 (20250101)

U.S. Cl.:

CPCG01T1/20182 (20200501); H10F39/011 (20250101); H10F39/1898 (20250101); H10F39/804 (20250101);

Field of Classification Search

CPC:G01T (1/20182); G01T (1/20189); G01T (1/202); H10F (39/011); H10F (39/1898); H10F (39/804)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2007/0045554	12/2006	Wakamatsu	250/370.11	G01T 1/20189
2019/0041532	12/2018	Toyama	N/A	G01T 1/2023
2019/0353802	12/2018	Steinhauser	N/A	G01T 1/20181

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2002-048840	12/2001	JP	N/A
2002-048870	12/2001	JP	N/A
2002-164525	12/2001	JP	N/A
2003232858	12/2002	JP	N/A
4018472	12/2006	JP	N/A
2010-217148	12/2009	JP	N/A
2014-048061	12/2013	JP	N/A
201732838	12/2016	TW	N/A
WO 2013175972	12/2012	WO	H01J 37/244
WO-2018/173893	12/2017	WO	N/A
WO-2019/181640	12/2018	WO	N/A

OTHER PUBLICATIONS

International Preliminary Report on Patentability mailed Jul. 6, 2023 for PCT/JP2021/041000.
cited by applicant

Primary Examiner: Gunberg; Edwin C

Assistant Examiner: Toohey; Richard O

Attorney, Agent or Firm: Faegre Drinker Biddle & Reath LLP

Background/Summary

TECHNICAL FIELD

(1) The present disclosure relates to a radiation detector, a method for manufacturing a radiation detector, and a scintillator panel unit.

BACKGROUND ART

(2) A radiation detector has been known which includes a sensor panel having a light receiving surface, a scintillator panel disposed on the light receiving surface, and an adhesive layer disposed between the light receiving surface and the scintillator panel (see, for example, Patent Literature 1).

CITATION LIST

Patent Literature

(3) Patent Literature 1: Japanese Patent No. 4018472

Technical Problem

(4) In the radiation detector as described above, an increase in area of a radiation detection region is required as the area of the sensor panel is increased. However, when a scintillator layer is formed of a granular phosphor and a binder resin in the scintillator panel, the area of the scintillator panel is easily increased in order to increase the area of the radiation detection region, but a high-resolution radiological image is difficult to be obtained. Meanwhile, when the scintillator layer is formed of a plurality of columnar crystals in the scintillator panel, a high-resolution radiological image is easily obtained, but the area of the scintillator panel is difficult to be increased in order to increase the area of the radiation detection region.

(5) An object of the present disclosure is to provide a radiation detector capable of achieving both an increase in area of a radiation detection region and an increase in resolution of a radiological image, a method for manufacturing such a radiation detector, and a scintillator panel unit suitable for these.

Solution to Problem

(6) A radiation detector of one aspect of the present disclosure includes a sensor panel having a light receiving surface, a first scintillator panel and a second scintillator panel disposed on the light receiving surface in a state of being adjacent to each other along the light receiving surface, and an adhesive layer disposed between the light receiving surface and the first scintillator panel and between the light receiving surface and the second scintillator panel, in which the first scintillator panel has a first substrate and a first scintillator layer including a plurality of columnar crystals formed on the first substrate, the second scintillator panel has a second substrate and a second scintillator layer including a plurality of columnar crystals formed on the second substrate, the first scintillator panel is attached to the light receiving surface by the adhesive layer in a state where the first scintillator layer is positioned on the light receiving surface side with respect to the first substrate, the second scintillator panel is attached to the light receiving surface by the adhesive layer in a state where the second scintillator layer is positioned on the light receiving surface side with respect to the second substrate, an outer edge of the first substrate when viewed from the first scintillator layer side includes a first portion extending along the second scintillator panel, and the first scintillator layer reaches at least the first portion, an outer edge of the second substrate when viewed from the second scintillator layer side includes a second portion extending along the first scintillator panel, and the second scintillator layer reaches at least the second portion, and the adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

(7) In the radiation detector of one aspect of the present disclosure, the first scintillator panel and the second scintillator panel are disposed on the light receiving surface of the sensor panel in a state of being adjacent to each other along the light receiving surface of the sensor panel. In the first scintillator panel and the second scintillator panel, the first scintillator layer reaches the first portion extending along the second scintillator panel of the outer edge of the first substrate, and the second scintillator layer reaches the second portion extending along the first scintillator panel of the outer edge of the second substrate. Therefore, while each of the first scintillator panel and the second scintillator panel is configured in such a size that the plurality of columnar crystals can be reliably formed, one radiation detection region can be obtained by the first scintillator panel and the second scintillator panel. Moreover, the adhesive layer disposed between the light receiving surface of the sensor panel and the first scintillator panel and between the light receiving surface of the sensor panel and the second scintillator panel is provided continuous over the first scintillator panel and the second scintillator panel. Thereby, each of the first scintillator panel and the second scintillator panel can be prevented from being released from the light receiving surface of the sensor panel. Due to the above, according to the radiation detector of one aspect of the present disclosure, both of an increase in area of the radiation detection region and an increase in resolution of the radiological

image can be achieved.

(8) In the radiation detector of one aspect of the present disclosure, the first substrate and the second substrate each may have flexibility. According to this, improvement in workability when each of the first scintillator panel and the second scintillator panel is attached to the light receiving surface of the sensor panel can be achieved.

(9) In the radiation detector of one aspect of the present disclosure, the first scintillator panel may have a rectangular shape having a one-side length of 300 mm or more when viewed from a thickness direction of the first substrate, and the second scintillator panel may have a rectangular shape having a one-side length of 300 mm or more when viewed from a thickness direction of the second substrate. According to this, an increase in area of the radiation detection region can be easily and reliably achieved.

(10) In the radiation detector of one aspect of the present disclosure, the adhesive layer may contain a pressure-sensitive adhesive or an adhesive. According to this, each of the first scintillator panel and the second scintillator panel can be reliably attached to the light receiving surface of the sensor panel.

(11) In the radiation detector of one aspect of the present disclosure, the first scintillator panel may further have a first protective layer covering the first substrate and the first scintillator layer, and the second scintillator panel may further have a second protective layer covering the second substrate and the second scintillator layer. According to this, the plurality of columnar crystals having deliquescent properties can be protected.

(12) The radiation detector of one aspect of the present disclosure may further include a first moisture-proof layer disposed on the first scintillator panel on a side opposite to the sensor panel, a second moisture-proof layer disposed on the second scintillator panel on a side opposite to the sensor panel, a first protective layer covering the first scintillator panel and the first moisture-proof layer, and a second protective layer covering the second scintillator panel and the second moisture-proof layer. According to this, the plurality of columnar crystals having deliquescent properties can be protected.

(13) The radiation detector of one aspect of the present disclosure may further include a granular phosphor disposed between the first scintillator panel and the second scintillator panel. According to this, deterioration of the image quality of a radiological image at a joint portion between the first scintillator panel and the second scintillator panel can be suppressed.

(14) A method for manufacturing a radiation detector of one aspect of the present disclosure is a method for manufacturing the aforementioned radiation detector, the method including a step of preparing the sensor panel, a step of preparing the first scintillator panel and the second scintillator panel, and a step of attaching each of the first scintillator panel and the second scintillator panel to the light receiving surface by the adhesive layer, in which in the attaching step, the adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

(15) According to the method for manufacturing the radiation detector of one aspect of the present disclosure, the aforementioned radiation detector can be easily and reliably obtained.

(16) In the method for manufacturing the radiation detector of one aspect of the present disclosure, in the attaching step, before each of the first scintillator panel and the second scintillator panel is attached to the light receiving surface, the adhesive layer may be disposed on each of the first scintillator panel and the second scintillator panel. According to this, the first scintillator panel, the second scintillator panel, and the adhesive layer can be handled in a state of being integrated with one another.

(17) In the method for manufacturing the radiation detector of one aspect of the present disclosure, in the attaching step, before each of the first scintillator panel and the second scintillator panel is attached to the light receiving surface, the adhesive layer may be disposed on the light receiving surface. According to this, the first scintillator panel and the second scintillator panel can be each independently handled.

(18) A scintillator panel unit of one aspect of the present disclosure includes an adhesive layer, and a first scintillator panel and a second scintillator panel disposed on the adhesive layer in a state of being adjacent to each other along the adhesive layer, in which the first scintillator panel has a first substrate and a first scintillator layer including a plurality of columnar crystals formed on the first substrate, the second scintillator panel has a second substrate and a second scintillator layer including a plurality of columnar crystals formed on the second substrate, the first scintillator panel is disposed on the adhesive layer in a state where the first scintillator layer is positioned on the adhesive layer side with respect to the first substrate, the second scintillator panel is disposed on the adhesive layer in a state where the second scintillator layer is positioned on the adhesive layer side with respect to the second substrate, an outer edge of the first substrate when viewed from the first scintillator layer side includes a first portion extending along the second scintillator panel, and the first scintillator layer reaches at least the first portion, an outer edge of the second substrate when viewed from the second scintillator layer side includes a second portion extending along the first scintillator panel, and the second scintillator layer reaches at least the second portion, and the adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

(19) According to the scintillator panel unit of one aspect of the present disclosure, the first scintillator panel, the second scintillator panel, and the adhesive layer can be handled in a state of being integrated with one another.

(20) In the scintillator panel unit of one aspect of the present disclosure, the first scintillator panel may further have a first protective layer covering the first substrate and the first scintillator layer, and the second scintillator panel may further have a second protective layer covering the second substrate and the second scintillator layer. According to this, the plurality of columnar crystals having deliquescent properties can be protected.

(21) The scintillator panel unit of one aspect of the present disclosure may further include a first moisture-proof layer disposed on the first scintillator panel on a side opposite to the adhesive layer, a second moisture-proof layer disposed on the second scintillator panel on a side opposite to the adhesive layer, a first protective layer covering the first scintillator panel and the first moisture-proof layer, and a second protective layer covering the second scintillator panel and the second moisture-proof layer. According to this, the plurality of columnar crystals having deliquescent properties can be protected.

Advantageous Effects of Invention

(22) According to the present disclosure, it is possible to provide a radiation detector capable of achieving both an increase in area of a radiation detection region and an increase in resolution of a radiological image, a method for manufacturing such a radiation detector, and a scintillator panel unit suitable for these.

Description

BRIEF DESCRIPTION OF DRAWINGS

(1) FIG. 1 is a cross-sectional view of a radiation detector of an embodiment.

(2) FIG. 2 is a cross-sectional view of a scintillator panel unit of an embodiment.

(3) FIG. 3 is a cross-sectional view of a radiation detector in one step of a method for manufacturing a radiation detector of an embodiment.

(4) FIG. 4 is a cross-sectional view of a radiation detector of a modification example.

(5) FIG. 5 is a cross-sectional view of a part of the radiation detector of the modification example.

(6) FIG. 6 is a cross-sectional view of a scintillator panel unit of a modification example.

(7) FIG. 7 is a cross-sectional view of a radiation detector of a modification example.

(8) FIG. 8 is a cross-sectional view of a radiation detector of a modification example.

(9) FIG. 9 is a cross-sectional view of a scintillator panel unit of a modification example.

(10) FIG. 10 is a cross-sectional view of a scintillator panel unit of a modification example.

DESCRIPTION OF EMBODIMENTS

(11) Hereinafter, embodiments of the present disclosure will be described in detail with reference to the drawings. Note that, in the drawings, the same or corresponding portions will be denoted by the same reference numerals, and redundant description thereof will not be provided.

(12) [Configuration of Radiation Detector]

(13) As illustrated in FIG. 1, a radiation detector 1 includes a sensor panel 2, a first scintillator panel 10, a second scintillator panel 20, an adhesive layer 3, a granular phosphor 4, a moisture-proof layer 5, an adhesive layer 6, and a sealing member 7. In the radiation detector 1, when a radial ray (for example, X ray) enters the first scintillator panel 10 and the second scintillator panel 20, scintillation light is generated in the first scintillator panel 10 and the second scintillator panel 20, and the scintillation light is detected by the sensor panel. The radiation detector 1 is used as a radiation imaging apparatus, for example, in a radiological image diagnostic apparatus for medical use or a nondestructive inspection apparatus.

(14) The sensor panel 2 includes a plurality of photoelectric conversion elements (not illustrated) disposed along a light receiving surface 2a. Each photoelectric conversion element constitutes a pixel and outputs an electrical signal according to the incident scintillation light. The light receiving surface 2a is provided on one main surface of the sensor panel 2. A surface 2b, which is a frame-shaped region encircling the light receiving surface 2a, is provided on the main surface. The sensor panel 2 has flexibility. The material for a substrate on which the plurality of photoelectric conversion elements are provided in the sensor panel 2 is, for example, PI (polyimide), PET (polyethylene terephthalate), PEN (polyethylene naphthalate), PP (polypropylene), PE (polyester), or PMMA (polymethyl methacrylate).

(15) The first scintillator panel 10 and the second scintillator panel 20 are disposed on the light receiving surface 2a in a state of being adjacent to each other along the light receiving surface 2a. The first scintillator panel 10 has a first substrate 11, a first scintillator layer 12, and a first protective layer 13. The second scintillator panel 20 has a second substrate 21, a second scintillator layer 22, and a second protective layer 23.

(16) The first substrate 11 and the second substrate 21 each have flexibility. The material for each of the first substrate 11 and the second substrate 21 is, for example, PET, PEN, PI, PP, PE, or PMMA. The thickness of each of the first substrate 11 and the second substrate 21 is, for example, 50 μm or more and 250 μm or less. Note that, a functional film may be formed on the front surface and the back surface of each of the first substrate 11 and the second substrate 21. This functional film is, for example, readily adhesive coating, antistatic coating, or a moisture-proof film (polyparaxylylene film). This functional film may be a laminate film including a plurality of films each having a different function.

(17) The first scintillator layer 12 includes a plurality of columnar crystals formed on the first substrate 11. The second scintillator layer 22 includes a plurality of columnar crystals formed on the second substrate 21. The plurality of columnar crystals are formed on the first substrate 11 or the second substrate 21, for example, by evaporating a scintillator material on the first substrate 11 or the second substrate 21. The material for each of the first scintillator layer 12 and the second scintillator layer 22 is, for example, CsI:Tl (cesium iodide containing thallium as an activator), CsI:Na (cesium iodide containing sodium as an activator), CsI:Ce (cesium iodide containing cerium as an activator), or CsI:Tl,Eu (cesium iodide containing thallium and europium as activators). The thickness of each of the first scintillator layer 12 and the second scintillator layer 22 is, for example, 100 μm or more and 1000 μm or less (preferably, 400 μm or more and 800 μm or less).

(18) The first protective layer 13 covers the first substrate 11 and the first scintillator layer 12. The second protective layer 23 covers the second substrate 21 and the second scintillator layer 22. The

material for each of the first protective layer **13** and the second protective layer **23** is, for example, parylene (polyparaxylene). The thickness of each of the first protective layer **13** and the second protective layer **23** is, for example, 0.5 μm or more and 20 μm or less.

(19) The first scintillator panel **10** is disposed on the light receiving surface **2a** in a state where the first scintillator layer **12** is positioned on the light receiving surface **2a** side with respect to the first substrate **11**. The first scintillator panel **10** has a rectangular shape having a one-side length of 300 mm or more when viewed from a thickness direction of the first substrate **11**. The second scintillator panel **20** is disposed on the light receiving surface **2a** in a state where the second scintillator layer **22** is positioned on the light receiving surface **2a** side with respect to the second substrate **21**. The second scintillator panel **20** has a rectangular shape having a one-side length of 300 mm or more when viewed from a thickness direction of the second substrate **21**.

(20) An outer edge **11a** of the first substrate **11** when viewed from the first scintillator layer **12** side includes a first portion **11b** extending along the second scintillator panel **20**. The first scintillator layer **12** reaches the first portion **11b**. In the present embodiment, the first scintillator layer **12** reaches the entire portion of the outer edge **11a**. An outer edge **21a** of the second substrate **21** when viewed from the second scintillator layer **22** side includes a second portion **21b** extending along the first scintillator panel **10**. The second scintillator layer **22** reaches the second portion **21b**. In the present embodiment, the second scintillator layer **22** reaches the entire portion of the outer edge **21a**. The first portion **11b** of the outer edge **11a** of the first substrate **11** and the second portion **21b** of the outer edge **21a** of the second substrate **21** face each other.

(21) Note that, the first substrate **11** and the first scintillator layer **12** are obtained by forming a scintillator layer including portions corresponding to a plurality of the first scintillator layers **12** on a substrate including portions corresponding to a plurality of the first substrates **11** and then cutting the substrate and the scintillator layer. The second substrate **21** and the second scintillator layer **22** are obtained by forming a scintillator layer including portions corresponding to a plurality of the second scintillator layers **22** on a substrate including portions corresponding to a plurality of the second substrates **21** and then cutting the substrate and the scintillator layer. The first substrate **11** and the first scintillator layer **12** may be obtained by forming a scintillator layer including a portion corresponding to one first scintillator layer **12** on a substrate including a portion corresponding to one first substrate **11** and then clipping the substrate and the scintillator layer. The second substrate **21** and the second scintillator layer **22** may be obtained by forming a scintillator layer including a portion corresponding to one second scintillator layer **22** on a substrate including a portion corresponding to one second substrate **21** and then clipping the substrate and the scintillator layer.

(22) A first angle θ_1 formed by a surface **10a** on the sensor panel **2** side (the first scintillator layer **12** side with respect to the first substrate **11**) in the first scintillator panel **10** and a side surface **10b** on the second scintillator panel **20** side in the first scintillator panel **10** is 45 degrees or more and less than 90 degrees. In the present embodiment, the surface **10a** and the entire side surface of the first scintillator panel **10** form an angle of 45 degrees or more and less than 90 degrees. A second angle θ_2 formed by a surface **20a** on the sensor panel **2** side (the second scintillator layer **22** side with respect to the second substrate **21**) in the second scintillator panel **20** and a side surface **20b** on the first scintillator panel **10** side in the second scintillator panel **20** is 45 degrees or more and less than 90 degrees. In the present embodiment, the surface **20a** and the entire side surface of the second scintillator panel **20** form an angle of 45 degrees or more and less than 90 degrees. A corner portion of the first scintillator panel **10** formed by the surface **10a** and the side surface **10b** is in contact with a corner portion of the second scintillator panel **20** formed by the surface **20a** and the side surface **20b**.

(23) The adhesive layer **3** is disposed between the light receiving surface **2a** and the first scintillator panel **10** and between the light receiving surface **2a** and the second scintillator panel **20**. The first scintillator panel **10** is attached to the light receiving surface **2a** by the adhesive layer **3** in a state where the first scintillator layer **12** is positioned on the light receiving surface **2a** side with respect

to the first substrate **11**. The second scintillator panel **20** is attached to the light receiving surface **2a** by the adhesive layer **3** in a state where the second scintillator layer **22** is positioned on the light receiving surface **2a** side with respect to the second substrate **21**. The adhesive layer **3** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. That is, the adhesive layer **3** is not separated for each of the first scintillator panel **10** and the second scintillator panel **20** but is integrally formed.

(24) The adhesive layer **3** is a pressure-sensitive adhesive or an adhesive. The pressure-sensitive adhesive means one not cured after adhesion. The adhesive means one cured after adhesion. The material for the adhesive layer **3** is, for example, a light transmissive organic material (for example, OCA (Optical Clear Adhesive)). The thickness of the adhesive layer **3** is, for example, 0.1 μm or more and 100 μm or less (preferably, 25 μm or less).

(25) The granular phosphor **4** is disposed between the first scintillator panel **10** and the second scintillator panel **20**. More specifically, the granular phosphor **4** is disposed in a groove with a V-shaped cross section formed by the side surface **10b** of the first scintillator panel **10** and the side surface **20b** of the second scintillator panel **20**. The material for the granular phosphor **4** is, for example, GOS (gadolinium oxysulfide).

(26) The moisture-proof layer **5** covers the first scintillator panel **10** and the second scintillator panel **20** on the sensor panel **2**. The moisture-proof layer **5** is disposed on the first scintillator panel **10** and the second scintillator panel **20** on a side opposite to the sensor panel **2** and is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. An outer edge **5a** of the moisture-proof layer **5** reaches the surface **2b** of the sensor panel **2** (the surface around the light receiving surface **2a**).

(27) The moisture-proof layer **5** has a main body layer **51** and an inorganic layer **52**. The main body layer **51** has flexibility. The inorganic layer **52** is disposed on the main body layer **51**. The inorganic layer **52** is attached to, for example, the main body layer **51** so as to be integrated with the main body layer **51**. The moisture-proof layer **5** is disposed on the first scintillator panel **10** and the second scintillator panel **20** in a state where the inorganic layer **52** is positioned on a side of the first scintillator panel **10** and the second scintillator panel **20** with respect to the main body layer **51**.

(28) The material for the main body layer **51** is, for example, PET, PEN, PI, PP, PE, or PMMA. The thickness of the main body layer **51** is, for example, 50 μm or more and 250 μm or less. The material for the inorganic layer **52** is, for example, Al (aluminum), Cu (copper), Ti (titanium), Fe (iron), or SUS (stainless steel). The thickness of the inorganic layer **52** is, for example, 10 μm or more and 100 μm or less.

(29) The adhesive layer **6** is disposed between the first scintillator panel **10** and the moisture-proof layer **5**, between the second scintillator panel **20** and the moisture-proof layer **5**, and between the surface **2b** of the sensor panel **2** and the moisture-proof layer **5**. The moisture-proof layer **5** is attached to the first scintillator panel **10**, the second scintillator panel **20**, and the surface **2b** of the sensor panel **2**. The adhesive layer **6** is a pressure-sensitive adhesive or an adhesive. The thickness of the adhesive layer **6** is, for example, 0.1 μm or more and 100 μm or less (preferably, 25 μm or less).

(30) The sealing member **7** seals the outer edge **5a** of the moisture-proof layer **5** in the surface **2b** of the sensor panel **2**. The sealing member **7** extends along the outer edge **5a** in a frame shape. The material for the sealing member **7** is, for example, epoxy, silicone, fluorine, urethane, or acryl. The material for the sealing member **7** may include a filler material formed of an inorganic material such as glass. The material for the filler material may have moisture-proof properties higher than the moisture-proof properties of the main material for the sealing member **7**, and is, for example, SiO.sub.2 (silicon dioxide), Al.sub.2O.sub.3 (aluminum oxide), or TiO.sub.2 (titanium oxide).

(31) As described above, in the radiation detector **1**, the first scintillator panel **10** and the second scintillator panel **20** are disposed on the light receiving surface **2a** of the sensor panel **2** in a state of

being adjacent to each other along the light receiving surface **2a** of the sensor panel **2**. In the first scintillator panel **10** and the second scintillator panel **20**, the first scintillator layer **12** reaches the first portion **11b** extending along the second scintillator panel **20** of the outer edge **11a** of the first substrate **11**, and the second scintillator layer **22** reaches the second portion **21b** extending along the first scintillator panel **10** of the outer edge **21a** of the second substrate **21**. Therefore, while each of the first scintillator panel **10** and the second scintillator panel **20** is configured in such a size that the plurality of columnar crystals can be reliably formed, one radiation detection region can be obtained by the first scintillator panel **10** and the second scintillator panel **20**. Moreover, the adhesive layer **3** disposed between the light receiving surface **2a** and the first scintillator panel **10** and between the light receiving surface **2a** and the second scintillator panel **20** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. Thereby, each of the first scintillator panel **10** and the second scintillator panel **20** can be prevented from being released from the light receiving surface **2a**. Due to the above, according to the radiation detector **1**, both of an increase in area of the radiation detection region and an increase in resolution of the radiological image can be achieved.

(32) In the radiation detector **1**, the first substrate **11** and the second substrate **21** each have flexibility. Thereby, improvement in workability when each of the first scintillator panel **10** and the second scintillator panel **20** is attached to the light receiving surface **2a** can be achieved.

(33) In the radiation detector **1**, the first scintillator panel **10** has a rectangular shape having a one-side length of 300 mm or more when viewed from the thickness direction of the first substrate **11**, and the second scintillator panel **20** has a rectangular shape having a one-side length of 300 mm or more when viewed from the thickness direction of the second substrate **21**. Thereby, an increase in area of the radiation detection region can be easily and reliably achieved.

(34) In the radiation detector **1**, the adhesive layer **3** contains a pressure-sensitive adhesive or an adhesive. Thereby, each of the first scintillator panel **10** and the second scintillator panel **20** can be reliably attached to the light receiving surface **2a**.

(35) In the radiation detector **1**, the first scintillator panel **10** has the first protective layer **13** covering the first substrate **11** and the first scintillator layer **12**, and the second scintillator panel **20** has the second protective layer **23** covering the second substrate **21** and the second scintillator layer **22**. Thereby, the plurality of columnar crystals having deliquescent properties can be protected.

(36) In the radiation detector **1**, the granular phosphor **4** is disposed between the first scintillator panel **10** and the second scintillator panel **20**. Thereby, deterioration of the image quality of a radiological image at the joint portion between the first scintillator panel **10** and the second scintillator panel **20** can be suppressed.

(37) In the radiation detector **1**, the moisture-proof layer **5** disposed on the first scintillator panel **10** and the second scintillator panel **20** on a side opposite to the sensor panel **2** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. Thereby, moisture can be prevented from coming into the joint portion between the first scintillator panel **10** and the second scintillator panel **20**, and the plurality of columnar crystals having deliquescent properties can be reliably protected. Further, even when a difference in expansion and contraction due to a temperature change occurs between the sensor panel **2** and the first scintillator panel **10** and between the sensor panel **2** and the second scintillator panel **20**, the joint portion between the first scintillator panel **10** and the second scintillator panel **20** can be prevented from being released from the light receiving surface **2a**.

(38) In the radiation detector **1**, the moisture-proof layer **5** has the main body layer **51** having flexibility and the inorganic layer **52** disposed on the main body layer **51**, and the moisture-proof layer **5** is disposed on the first scintillator panel **10** and the second scintillator panel **20** in a state where the inorganic layer **52** is positioned on a side of the first scintillator panel **10** and the second scintillator panel **20** with respect to the main body layer **51**. Thereby, the inorganic layer **52** can function as the moisture-proof layer **5**, and the main body layer **51** can function as the protective

layer.

(39) In the radiation detector **1**, the first angle θ_1 formed by the surface **10a** on the sensor panel **2** side in the first scintillator panel **10** and the side surface **10b** on the second scintillator panel **20** side in the first scintillator panel **10** is 90 degrees or less, and the second angle θ_2 formed by the surface **20a** on the sensor panel **2** side in the second scintillator panel **20** and the side surface **20b** on the first scintillator panel **10** side in the second scintillator panel **20** is 90 degrees or less. Thereby, the joint portion between the first scintillator panel **10** and the second scintillator panel **20** can be prevented from being released from the light receiving surface **2a** due to thermal expansion of air at the joint portion. Further, since the first scintillator layer **12** and the second scintillator layer **22** come close to each other, deterioration of the image quality of a radiological image at the joint portion between the first scintillator panel **10** and the second scintillator panel **20** can be suppressed.

(40) In the radiation detector **1**, each of the first angle θ_1 and the second angle θ_2 is 45 degrees or more and less than 90 degrees. Thereby, the joint portion between the first scintillator panel **10** and the second scintillator panel **20** can be more reliably prevented from being released from the light receiving surface **2a** due to thermal expansion of air at the joint portion.

(41) In the radiation detector **1**, each of the first angle θ_1 and the second angle θ_2 is less than 90 degrees, and the sensor panel **2** has flexibility. Thereby, the entire radiation detector **1** can be deflected according to the installation environment of the radiation detector **1**, and the like. Further, when the entire radiation detector **1** is deflected such that the sensor panel **2** is located outside with respect to the first scintillator panel **10** and the second scintillator panel **20**, the first scintillator panel **10** and the second scintillator panel **20** can be prevented from physically interfering with each other.

(42) As an example, as illustrated in FIG. 4, the entire radiation detector **1** can be deflected such that the first scintillator panel **10** and the second scintillator panel **20** are disposed along a cylindrical surface S. At this time, since each of the first angle θ_1 and the second angle θ_2 is less than 90 degrees, the first scintillator panel **10** and the second scintillator panel **20** can be prevented from physically interfering with each other. Note that, the radiation detector **1** illustrated in FIG. 4 does not include the granular phosphor **4**, the moisture-proof layer **5**, the adhesive layer **6**, and the sealing member **7**, but may include these members as necessary.

(43) [Configuration of Scintillator Panel Unit]

(44) As illustrated in FIG. 2, a scintillator panel unit **100** includes a first scintillator panel **10**, a second scintillator panel **20**, an adhesive layer **3**, and a release sheet **8**. The scintillator panel unit **100** is used, for example, when the radiation detector **1** is manufactured.

(45) The first scintillator panel **10** and the second scintillator panel **20** are disposed on the adhesive layer **3** as a support layer in a state of being adjacent to each other along the adhesive layer **3**. The adhesive layer **3** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. The release sheet **8** covers the adhesive layer **3** from a side opposite to the first scintillator panel **10** and the second scintillator panel **20**. The adhesive force of the adhesive layer **3** with respect to a surface **8a** of the release sheet **8** is lower than the adhesive force of the adhesive layer **3** with respect to the first scintillator panel **10** and the second scintillator panel **20**. Note that, in the scintillator panel unit **100**, the adhesive layer **3** is a pressure-sensitive adhesive layer.

(46) The first scintillator panel **10** is disposed on the adhesive layer **3** in a state where the first scintillator layer **12** is positioned on the adhesive layer **3** side with respect to the first substrate **11**. The second scintillator panel **20** is disposed on the adhesive layer **3** in a state where the second scintillator layer **22** is positioned on the adhesive layer **3** side with respect to the second substrate **21**. That is, the method of disposing the first scintillator panel **10** and the second scintillator panel **20** on the adhesive layer **3** of the scintillator panel unit **100** is the same as the method of disposing the first scintillator panel **10** and the second scintillator panel **20** on the adhesive layer **3** of the radiation detector **1** described above.

(47) According to the scintillator panel unit **100** described above, the first scintillator panel **10**, the second scintillator panel **20**, and the adhesive layer **3** can be handled in a state of being integrated with one another.

(48) In the scintillator panel unit **100**, the first scintillator panel **10** has a first protective layer **13** covering the first substrate **11** and the first scintillator layer **12**, and the second scintillator panel **20** has a second protective layer **23** covering the second substrate **21** and the second scintillator layer **22**. Thereby, the plurality of columnar crystals having deliquescent properties can be protected.

(49) [Method for Manufacturing Radiation Detector]

(50) A method for manufacturing the radiation detector **1** will be described. In the present embodiment, the aforementioned scintillator panel unit **100** is used.

(51) First, the sensor panel **2** is prepared (a step of preparing the sensor panel **2**). Subsequently, in a state of the scintillator panel unit **100** illustrated in FIG. **2**, the first scintillator panel **10** and the second scintillator panel **20** are prepared (a step of preparing the first scintillator panel **10** and the second scintillator panel **20**). In the step of preparing the first scintillator panel **10** and the second scintillator panel **20**, each of the first angle θ_1 and the second angle θ_2 is 45 degrees or more and less than 90 degrees (see FIG. **1**). Note that, any one of the step of preparing the sensor panel **2** and the step of preparing the first scintillator panel **10** and the second scintillator panel **20** may be previously performed, and both of the steps may be simultaneously performed.

(52) Subsequently, the release sheet **8** is released from the adhesive layer **3** of the scintillator panel unit **100**, and as illustrated in FIG. **3**, each of the first scintillator panel **10** and the second scintillator panel **20** is attached to the light receiving surface **2a** by the adhesive layer **3** (an attaching step). That is, each of the first scintillator panel **10** and the second scintillator panel **20** is disposed on the light receiving surface **2a** (a step of disposing each of the first scintillator panel **10** and the second scintillator panel **20**). In the attaching step, the adhesive layer **3** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. In the attaching step, before each of the first scintillator panel **10** and the second scintillator panel **20** is attached to the light receiving surface **2a**, the adhesive layer **3** is disposed on each of the first scintillator panel **10** and the second scintillator panel **20**.

(53) In the attaching step, since the first substrate **11** and the second substrate **21** each have flexibility, while the first scintillator panel **10** and the second scintillator panel **20** are deflected, each of the first scintillator panel **10** and the second scintillator panel **20** can be gradually attached to the light receiving surface **2a** from one side. At this time, the corner portion of the second scintillator panel **20** formed by the surface **20a** and the side surface **20b** can be reliably brought into contact with the corner portion of the first scintillator panel **10** formed by the surface **10a** and the side surface **10b**.

(54) Subsequently, as illustrated in FIG. **1**, the first scintillator panel **10** and the second scintillator panel **20** are covered with the moisture-proof layer **5** on the sensor panel **2**. That is, the moisture-proof layer **5** is disposed on the first scintillator panel **10** and the second scintillator panel **20** on a side opposite to the sensor panel **2** (a step of disposing the moisture-proof layer **5**). In the step of disposing the moisture-proof layer **5**, the moisture-proof layer **5** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. Subsequently, in the surface **2b** of the sensor panel **2**, the outer edge **5a** of the moisture-proof layer **5** is sealed by the sealing member **7** to obtain the radiation detector **1**. In the present embodiment, the step of disposing each of the first scintillator panel **10** and the second scintillator panel **20** is performed before the step of disposing the moisture-proof layer **5**.

(55) According to the method for manufacturing the radiation detector **1** described above, the aforementioned radiation detector **1** can be easily and reliably obtained.

(56) In the method for manufacturing the radiation detector **1**, in the attaching step, before each of the first scintillator panel **10** and the second scintillator panel **20** is attached to the light receiving surface **2a**, the adhesive layer **3** is disposed on each of the first scintillator panel **10** and the second

scintillator panel **20**. Thereby, the first scintillator panel **10**, the second scintillator panel **20**, and the adhesive layer **3** can be handled in a state of being integrated with one another.

(57) In the method for manufacturing the radiation detector **1**, the step of disposing each of the first scintillator panel **10** and the second scintillator panel **20** is performed before the step of disposing the moisture-proof layer **5**. Thereby, when the moisture-proof layer **5** is disposed on the first scintillator panel **10** and the second scintillator panel **20** on a side opposite to the sensor panel **2**, the sensor panel **2**, the first scintillator panel **10**, and the second scintillator panel **20** can be handled in a state of being integrated with one another.

MODIFICATION EXAMPLE

(58) The present disclosure is not limited to the aforementioned embodiments. In the radiation detector **1**, as illustrated in (a) of FIG. 5, each of the first angle θ_1 and the second angle θ_2 may be 90 degrees. Alternatively, in the radiation detector **1**, as illustrated in (b) of FIG. 5, each of the first angle θ_1 and the second angle θ_2 may exceed 90 degrees. In this case, the granular phosphor **4** may be disposed between the side surface **10b** of the first scintillator panel **10** and the side surface **20b** of the second scintillator panel **20**. The same fact that each of the first angle θ_1 and the second angle θ_2 may be 90 degrees or more as described above applies in the scintillator panel unit **100** and the method for manufacturing the radiation detector **1** described above.

(59) As illustrated in FIG. 6, the scintillator panel unit **100** may include the moisture-proof layer **5** as a support layer, and the first scintillator panel **10** and the second scintillator panel **20** disposed on the moisture-proof layer **5** in a state of being adjacent to each other along the moisture-proof layer **5**. The configuration of the scintillator panel unit **100** illustrated in FIG. 6 is as follows. That is, the moisture-proof layer **5** is provided continuous over the first scintillator panel **10** and the second scintillator panel **20**. The first scintillator panel **10** is disposed on the moisture-proof layer **5** in a state where the first substrate **11** is positioned on the moisture-proof layer **5** side with respect to the first scintillator layer **12**. The second scintillator panel **20** is disposed on the moisture-proof layer **5** in a state where the second substrate **21** is positioned on the moisture-proof layer **5** side with respect to the second scintillator layer **22**.

(60) In the scintillator panel unit **100** illustrated in FIG. 6, the moisture-proof layer **5** covers the first scintillator panel **10** and the second scintillator panel **20**, and the adhesive layer **6** is disposed between the first scintillator panel **10** and the moisture-proof layer **5** and between the second scintillator panel **20** and the moisture-proof layer **5**. Further, the adhesive layer **3** is disposed between the first scintillator panel **10** and the release sheet **8** and between the second scintillator panel **20** and the release sheet **8**, and the adhesive layer **6** is disposed between the outer edge **5a** of the moisture-proof layer **5** and the release sheet **8**. The adhesive layer **3** and the adhesive layer **6** each are a pressure-sensitive adhesive layer. The adhesive force of the adhesive layer **3** with respect to the surface **8a** of the release sheet **8** is lower than the adhesive force of the adhesive layer **3** with respect to the first scintillator panel **10** and the second scintillator panel **20**. The adhesive force of the adhesive layer **6** with respect to the surface **8a** of the release sheet **8** is lower than the adhesive force of the adhesive layer **6** with respect to the outer edge **5a** of the moisture-proof layer **5**.

According to the scintillator panel unit **100** illustrated in FIG. 6, the first scintillator panel **10**, the second scintillator panel **20**, and the moisture-proof layer **5** can be handled in a state of being integrated with one another. Note that, the scintillator panel unit **100** illustrated in FIG. 6 may not include the adhesive layer **3**, a portion of the adhesive layer **6** disposed on the outer edge **5a**, and the release sheet **8**.

(61) As illustrated in FIG. 7, in the radiation detector **1**, the outer edge of the moisture-proof layer **5** may be positioned on the first scintillator panel **10** and the second scintillator panel **20**, and the sealing member **7** may seal the side surfaces outside the first scintillator panel **10** and the second scintillator panel **20** and the side surface outside the moisture-proof layer **5** in the surface **2b** of the sensor panel **2**.

(62) As illustrated in FIG. 8, in the radiation detector **1**, a first moisture-proof layer **5A** may be

disposed on the first scintillator panel **10** on a side opposite to the sensor panel **2**, and a second moisture-proof layer **5B** may be disposed on the second scintillator panel **20** on a side opposite to the sensor panel **2**. In this case, the first protective layer **13** may cover the first scintillator panel **10** and the first moisture-proof layer **5A**, and the second protective layer **23** may cover the second scintillator panel **20** and the second moisture-proof layer **5B**. The configurations of the first moisture-proof layer **5A** and the second moisture-proof layer **5B** are the same as the configuration of the moisture-proof layer **5** described above. In the radiation detector **1** illustrated in FIG. **8**, the sealing member **7** seals the side surfaces outside the first scintillator panel **10** and the second scintillator panel **20** and the side surfaces outside of the first moisture-proof layer **5A** and the second moisture-proof layer **5B**, in the surface **2b** of the sensor panel **2**. According to the radiation detector **1** illustrated in FIG. **8**, the plurality of columnar crystals having deliquescent properties can be protected.

(63) As illustrated in FIG. **9**, in the scintillator panel unit **100**, the outer edge of the moisture-proof layer **5** may be positioned on the first scintillator panel **10** and the second scintillator panel **20**. Note that, the scintillator panel unit **100** illustrated in FIG. **9** may not include the adhesive layer **3** and the release sheet **8**.

(64) As illustrated in FIG. **10**, in the scintillator panel unit **100**, the first moisture-proof layer **5A** may be disposed on the first scintillator panel **10** on a side opposite to the adhesive layer **3**, and the second moisture-proof layer **5B** may be disposed on the second scintillator panel **20** on a side opposite to the adhesive layer **3**. In this case, the first protective layer **13** may cover the first scintillator panel **10** and the first moisture-proof layer **5A**, and the second protective layer **23** may cover the second scintillator panel **20** and the second moisture-proof layer **5B**. The configurations of the first moisture-proof layer **5A** and the second moisture-proof layer **5B** are the same as the configuration of the moisture-proof layer **5** described above. According to the scintillator panel unit **100** illustrated in FIG. **10**, the plurality of columnar crystals having deliquescent properties can be protected.

(65) In the radiation detector **1** and the scintillator panel unit **100**, the first substrate **11** and the second substrate **21** each may not have flexibility. In this case, the material for each of the first substrate **11** and the second substrate **21** may be, for example, CFRP (carbon fiber reinforced plastic), a-C (amorphous carbon), Al, Cu, or glass. When the material for each of the first substrate **11** and the second substrate **21** is a metal, a functional film (such as a polyparaxylene film) may be formed, for example, as corrosion-resistant coating, on the front surface and the back surface of each of the first substrate **11** and the second substrate **21**. This functional film may be a laminate film including a plurality of films each having a different function. As an example, when the material for each of the first substrate **11** and the second substrate **21** is Al, an alumite (anodized alumina) film and a polyparaxylene film may be formed on the front surface and the back surface of each of the first substrate **11** and the second substrate **21**. In the radiation detector **1** and the scintillator panel unit **100**, each of the first substrate **11** and the second substrate **21** may be a laminate substrate including a plurality of substrates (for example, a CFRP substrate and a PET substrate).

(66) In the radiation detector **1** and the scintillator panel unit **100**, the first scintillator layer **12** may reach at least the first portion **11b** of the outer edge **11a** of the first substrate **11**. Similarly, the second scintillator layer **22** may reach at least the second portion **21b** of the outer edge **11a** of the second substrate **21**. In the radiation detector **1** and the scintillator panel unit **100**, the first substrate **11** and the first scintillator layer **12** are not limited to those obtained by cutting or clipping, and the first scintillator layer **12** may reach the side surface of the first substrate **11**. Similarly, the second substrate **21** and the second scintillator layer **22** are not limited to those obtained by cutting or clipping, and the second scintillator layer **22** may reach the side surface of the second substrate **21**.

(67) In the radiation detector **1**, the sensor panel **2** may not have flexibility. In this case, the material for the substrate provided with a plurality of photoelectric conversion elements in the

sensor panel 2 is, for example, a-Si (amorphous silicon), Si (silicon), or glass (for example, alkali-free glass). In the radiation detector 1, the outer edge 5a of the moisture-proof layer 5 may reach the surface 2b of the sensor panel 2 around the light receiving surface 2a, and the sealing member 7 may seal the outer edge 5a of the moisture-proof layer 5 in the surface 2b of the sensor panel 2 in a state where a region defined by the sensor panel 2 and the moisture-proof layer 5 is decompressed. In this case, the moisture-proof layer 5 can be brought into close contact with the first scintillator panel 10 and the second scintillator panel 20 without using the adhesive layer 3. In the radiation detector 1, the moisture-proof layer 5 formed in a hat shape may cover the first scintillator panel 10 and the second scintillator panel 20 in the sensor panel 2, and the sealing member 7 may seal the outer edge 5a of the moisture-proof layer 5 in the surface 2b of the sensor panel 2.

(68) The radiation detector 1 and the scintillator panel unit 100 may not include the moisture-proof layers 5, 5A, and 5B. The radiation detector 1 and the scintillator panel unit 100 may not include the first protective layer 13 and the second protective layer 23.

(69) In the method for manufacturing the radiation detector 1, in the attaching step, before each of the first scintillator panel 10 and the second scintillator panel 20 is attached to the light receiving surface 2a, the adhesive layer 3 may be disposed on the light receiving surface 2a. In this case, the first scintillator panel 10 and the second scintillator panel 20 can be each independently handled. In the method for manufacturing the radiation detector 1, the step of disposing the moisture-proof layer 5 may be performed before the step of disposing each of the first scintillator panel 10 and the second scintillator panel 20. In this case, when each of the first scintillator panel 10 and the second scintillator panel 20 is disposed on the light receiving surface 2a, the first scintillator panel 10, the second scintillator panel 20, and the moisture-proof layer 5 can be handled in a state of being integrated with one another.

(70) All of embodiments, modification examples, and the like of the radiation detector 1, the scintillator panel unit 100, and the method for manufacturing the radiation detector 1 described above may include, as a plurality of scintillator panels disposed one-dimensionally or two-dimensionally, the first scintillator panel 10 and the second scintillator panel 20. For example, when three scintillator panels are disposed one-dimensionally, any “two adjacent scintillator panels” can be regarded as the first scintillator panel 10 and the second scintillator panel 20. Furthermore, when four scintillator panels are disposed two-dimensionally, any “two adjacent scintillator panels” can be regarded as the first scintillator panel 10 and the second scintillator panel 20.

REFERENCE SIGNS LIST

(71) 1: radiation detector, 2: sensor panel, 2a: light receiving surface, 3: adhesive layer, 4: granular phosphor, 5A: first moisture-proof layer, 5B: second moisture-proof layer, 10: first scintillator panel, 11: first substrate, 11a: outer edge, 11b: first portion, 12: first scintillator layer, 13: first protective layer, 20: second scintillator panel, 21: second substrate, 21a: outer edge, 21b: second portion, 22: second scintillator layer, 23: second protective layer, 100: scintillator panel unit.

Claims

1. A radiation detector comprising: a sensor panel having a light receiving surface; a first scintillator panel and a second scintillator panel disposed on the light receiving surface in a state of being adjacent to each other along the light receiving surface; and an adhesive layer disposed between the light receiving surface and the first scintillator panel and between the light receiving surface and the second scintillator panel, wherein the first scintillator panel has a first substrate and a first scintillator layer including a plurality of columnar crystals formed on the first substrate, the second scintillator panel has a second substrate and a second scintillator layer including a plurality of columnar crystals formed on the second substrate, the first scintillator panel is attached to the light receiving surface by the adhesive layer in a state where the first scintillator layer is positioned

on the light receiving surface side with respect to the first substrate, the second scintillator panel is attached to the light receiving surface by the adhesive layer in a state where the second scintillator layer is positioned on the light receiving surface side with respect to the second substrate, an outer edge of the first substrate when viewed from the first scintillator layer side includes a first portion extending along the second scintillator panel, and the first scintillator layer reaches at least the first portion, an outer edge of the second substrate when viewed from the second scintillator layer side includes a second portion extending along the first scintillator panel, and the second scintillator layer reaches at least the second portion, and the adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

2. The radiation detector according to claim 1, wherein the first substrate and the second substrate each have flexibility.

3. The radiation detector according to claim 1, wherein the first scintillator panel has a rectangular shape having a one-side length of 300 mm or more when viewed from a thickness direction of the first substrate, and the second scintillator panel has a rectangular shape having a one-side length of 300 mm or more when viewed from a thickness direction of the second substrate.

4. The radiation detector according to claim 1, wherein the adhesive layer contains a pressure-sensitive adhesive or an adhesive.

5. The radiation detector according to claim 1, wherein the first scintillator panel further has a first protective layer covering the first substrate and the first scintillator layer, and the second scintillator panel further has a second protective layer covering the second substrate and the second scintillator layer.

6. The radiation detector according to claim 1, further comprising: a first moisture-proof layer disposed on the first scintillator panel on a side opposite to the sensor panel; a second moisture-proof layer disposed on the second scintillator panel on a side opposite to the sensor panel; a first protective layer covering the first scintillator panel and the first moisture-proof layer; and a second protective layer covering the second scintillator panel and the second moisture-proof layer.

7. The radiation detector according to claim 1, further comprising a granular phosphor disposed between the first scintillator panel and the second scintillator panel.

8. A method for manufacturing the radiation detector according to claim 1, the method comprising: a step of preparing the sensor panel; a step of preparing the first scintillator panel and the second scintillator panel; and a step of attaching each of the first scintillator panel and the second scintillator panel to the light receiving surface by the adhesive layer, wherein in the attaching step, the adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

9. The method for manufacturing the radiation detector according to claim 8, wherein in the attaching step, before each of the first scintillator panel and the second scintillator panel is attached to the light receiving surface, the adhesive layer is disposed on each of the first scintillator panel and the second scintillator panel.

10. The method for manufacturing the radiation detector according to claim 8, wherein in the attaching step, before each of the first scintillator panel and the second scintillator panel is attached to the light receiving surface, the adhesive layer is disposed on the light receiving surface.

11. The radiation detector according to claim 1, wherein at least one first scintillator panel as the first scintillator panel and one second scintillator panel as the second scintillator panel are disposed on one sensor panel as the sensor panel, with the adhesive layer interposed therebetween, and the adhesive layer is provided continuous over the one first scintillator panel and the one second scintillator panel on the one sensor panel.

12. A scintillator panel unit comprising: an adhesive layer; and a first scintillator panel and a second scintillator panel disposed on the adhesive layer in a state of being adjacent to each other along the adhesive layer, wherein the first scintillator panel has a first substrate and a first scintillator layer including a plurality of columnar crystals formed on the first substrate, the second

scintillator panel has a second substrate and a second scintillator layer including a plurality of columnar crystals formed on the second substrate, the first scintillator panel is disposed on the adhesive layer in a state where the first scintillator layer is positioned on the adhesive layer side with respect to the first substrate, the second scintillator panel is disposed on the adhesive layer in a state where the second scintillator layer is positioned on the adhesive layer side with respect to the second substrate, an outer edge of the first substrate when viewed from the first scintillator layer side includes a first portion extending along the second scintillator panel, and the first scintillator layer reaches at least the first portion, an outer edge of the second substrate when viewed from the second scintillator layer side includes a second portion extending along the first scintillator panel, and the second scintillator layer reaches at least the second portion, and the adhesive layer is provided continuous over the first scintillator panel and the second scintillator panel.

13. The scintillator panel unit according to claim 12, wherein the first scintillator panel further has a first protective layer covering the first substrate and the first scintillator layer, and the second scintillator panel further has a second protective layer covering the second substrate and the second scintillator layer.

14. The scintillator panel unit according to claim 12, further comprising: a first moisture-proof layer disposed on the first scintillator panel on a side opposite to the adhesive layer; a second moisture-proof layer disposed on the second scintillator panel on a side opposite to the adhesive layer; a first protective layer covering the first scintillator panel and the first moisture-proof layer; and a second protective layer covering the second scintillator panel and the second moisture-proof layer.
