

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408453
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Kim; Kook-tae et al.

Image sensor

Abstract

An image sensor including a semiconductor substrate having a first surface and a second surface; and a pixel isolation film extending from the first surface of the semiconductor substrate into the semiconductor substrate and defining active pixels in the semiconductor substrate, wherein the pixel isolation film includes a buried conductive layer including polysilicon containing a fining element at a first concentration; and an insulating liner between the buried conductive layer and the semiconductor substrate, and wherein the fining element includes oxygen, carbon, or fluorine.

Inventors: Kim; Kook-tae (Hwaseong-si, KR), Kim; Jin-gyun (Hwaseong-si, KR), Hong; Soo-jin (Guri-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 70459098

Assignee: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)

Appl. No.: 18/731895

Filed: June 03, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240321910 A1	Sep. 26, 2024

Foreign Application Priority Data

KR	10-2018-0135331	Nov. 06, 2018
----	-----------------	---------------

Related U.S. Application Data

continuation parent-doc US 18144969 20230509 US 12068337 child-doc US 18731895
continuation parent-doc US 17519701 20211105 US 11652113 20230516 child-doc US 18144969

Publication Classification

Int. Cl.: H10F39/00 (20250101)

U.S. Cl.:

CPC H10F39/8023 (20250101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6444390	12/2001	Yamazaki et al.	N/A	N/A
9054003	12/2014	Ahn et al.	N/A	N/A
9160949	12/2014	Zhang et al.	N/A	N/A
9425231	12/2015	Kim et al.	N/A	N/A
9564463	12/2016	Ihara	N/A	N/A
9620546	12/2016	Chung et al.	N/A	N/A
9666624	12/2016	Lin et al.	N/A	N/A
10304887	12/2018	Kim et al.	N/A	N/A
10748955	12/2019	Oh et al.	N/A	N/A
11239269	12/2021	Kim et al.	N/A	N/A
11652113	12/2022	Kim	257/432	H10F 39/014
12068337	12/2023	Kim	N/A	H10F 39/8037
2008/0102557	12/2007	Kim et al.	N/A	N/A
2011/0079857	12/2010	Lee et al.	N/A	N/A
2012/0043600	12/2011	Van der Vegt et al.	N/A	N/A
2012/0098078	12/2011	Shim et al.	N/A	N/A
2013/0171807	12/2012	Yoo et al.	N/A	N/A
2013/0249061	12/2012	Murakoshi	N/A	N/A
2014/0374868	12/2013	Lee et al.	N/A	N/A
2015/0115388	12/2014	Eda et al.	N/A	N/A
2015/0243694	12/2014	Ihara	N/A	N/A
2016/0064430	12/2015	Lee et al.	N/A	N/A
2016/0172391	12/2015	Ihara	N/A	N/A
2017/0040358	12/2016	Kim et al.	N/A	N/A
2017/0170229	12/2016	Oh et al.	N/A	N/A
2017/0221983	12/2016	Srinivasan et al.	N/A	N/A
2018/0190691	12/2017	Lee et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
105047552	12/2014	CN	N/A
106856201	12/2016	CN	N/A
107068609	12/2016	CN	N/A
108695346	12/2017	CN	N/A
10-2012-0121176	12/2011	KR	N/A
10-2013-0128992	12/2012	KR	N/A
10-2014-0119648	12/2013	KR	N/A
10-2015-0101681	12/2014	KR	N/A
10-2016-0026299	12/2015	KR	N/A

OTHER PUBLICATIONS

Third Office Action dated May 31, 2024 for corresponding CN Patent Application No.

201911068784.0. cited by applicant

Notice Of Allowance, dated Sep. 26, 2023, for corresponding Korean Patent Application No. 10-2018-0135331. cited by applicant

Office Action, dated Nov. 22, 2023, for corresponding CN Patent Application No. 201911068784.0. cited by applicant

Chinese Office Action dated May 31, 2023 for corresponding Application No. 201911068784.0. cited by applicant

Korean Office Action dated Apr. 22, 2023 for corresponding Application No. 10-2018-0135331. cited by applicant

Primary Examiner: Green; Telly D

Attorney, Agent or Firm: Muir Patent Law, PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This is a continuation of U.S. patent application Ser. No. 18/144,969, filed May 9, 2023, which is a continuation of U.S. patent application Ser. No. 17/519,701, filed Nov. 5, 2021, now U.S. Pat. No. 11,652,113, which is a continuation of U.S. patent application Ser. No. 16/451,412, filed Jun. 25, 2019, now U.S. Pat. No. 11,239,269, which claims the benefit of priority under 35 U.S.C. § 119 of Korean Patent Application No. 10-2018-0135331, filed Nov. 6, 2018, in the Korean Intellectual Property Office, the entire contents of all of which are hereby incorporated by reference.

BACKGROUND

1. Field

(1) Embodiments relate to an image sensor.

2. Description of the Related Art

(2) An image sensor is a device that converts an optical image signal into an electric signal. The image sensor may include pixel region including a plurality of photodiode regions in which incident light is received and converted into the electrical signal, and a pixel isolation region for electrically separating pixels from each other.

SUMMARY

(3) The embodiments may be realized by providing an image sensor including a semiconductor substrate having a first surface and a second surface; and a pixel isolation film extending from the first surface of the semiconductor substrate into the semiconductor substrate and defining active

pixels in the semiconductor substrate, wherein the pixel isolation film includes a buried conductive layer including polysilicon containing a fining element at a first concentration; and an insulating liner between the buried conductive layer and the semiconductor substrate, and wherein the fining element includes oxygen, carbon, or fluorine.

(4) The embodiments may be realized by providing an image sensor including a semiconductor substrate; and a pixel isolation film in a pixel trench passing through the semiconductor substrate and defining active pixels in the semiconductor substrate, wherein the pixel isolation film includes an insulating liner on a sidewall of the pixel trench; and a buried conductive layer filled in an inside of the pixel trench on the insulating liner, the buried conductive layer including polysilicon containing a fining element at a first concentration, and wherein the fining element includes oxygen, carbon, or fluorine.

(5) The embodiments may be realized by providing an image sensor including a semiconductor substrate including a plurality of active pixels; and a pixel isolation film between active pixels of the plurality of active pixels and in a pixel trench passing through the semiconductor substrate, wherein the pixel isolation film includes: an insulating liner on a sidewall of the pixel trench; and a buried conductive layer filled in an inside of the pixel trench on the insulating liner, the buried conductive layer including polysilicon containing a fining element at a first concentration, and wherein the fining element includes oxygen and the first concentration is about 5 at % to about 40 at %.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

(2) FIG. 1 illustrates a layout view of an image sensor according to example embodiments;

(3) FIG. 2 illustrates a cross-sectional view taken along line II-II' of FIG. 1;

(4) FIG. 3 illustrates an equivalent circuit diagram of an active pixel of an image sensor according to example embodiments;

(5) FIG. 4 illustrates a cross-sectional view of an image sensor according to example embodiments;

(6) FIG. 5 illustrates a cross-sectional view of an image sensor according to example embodiments;

(7) FIG. 6 illustrates a cross-sectional view of an image sensor according to example embodiments;

(8) FIGS. 7A-7L illustrate cross-sectional views of stages in a method of manufacturing an image sensor according to example embodiments

(9) FIG. 8 illustrates a flowchart of a method of manufacturing an image sensor according to example embodiments;

(10) FIGS. 9A-9C illustrate cross-sectional views of stages in a method of manufacturing an image sensor according to example embodiments;

(11) FIG. 10 illustrates a flow chart of a method of manufacturing an image sensor in accordance with example embodiments;

(12) FIG. 11 illustrates a flowchart of a method of manufacturing an image sensor according to example embodiments;

(13) FIGS. 12A-12D illustrate cross-sectional views of stages in a method of manufacturing an image sensor according to example embodiments;

(14) FIG. 13 illustrates a flow chart of a method of manufacturing an image sensor in accordance with example embodiments;

(15) FIG. 14 illustrates a flowchart of a method of manufacturing an image sensor according to example embodiments; and

(16) FIG. 15 illustrates an X-ray diffraction analysis graph of a buried conductive layer included in

an image sensor according to an Example and Comparative Examples.

DETAILED DESCRIPTION

(17) FIG. 1 illustrates a layout diagram of an image sensor **100** according to example embodiments. FIG. 2 illustrates a cross-sectional view taken along line II-II' of FIG. 1.

(18) Referring to FIGS. 1 and 2, the image sensor **100** may include an active pixel region APR, a peripheral circuit region PCR, and a pad region PDR in or on a semiconductor substrate **110**.

(19) The active pixel region APR may include a plurality of active pixels PX and each of a plurality of photoelectric conversion regions **120** may be arranged in each of the plurality of active pixels PX. In the active pixel region APR, a plurality of active pixels PX may be arranged in a matrix shape in the form of rows and columns along first direction (for example, X direction in FIG. 1) parallel to an upper surface of the semiconductor substrate **110** and second direction (for example, Y direction in FIG. 1) parallel to the upper surface of the semiconductor substrate **110**.

(20) In an implementation, as illustrated, the peripheral circuit region PCR may be on one side of the active pixel region APR in a plan view. In an implementation, the peripheral circuit region PCR may surround an entirety of the active pixel region APR. In an implementation, unlike that shown in FIG. 1, the peripheral circuit region PCR may be on an additional substrate, and then the additional substrate may be attached to the semiconductor substrate **110**.

(21) The peripheral circuit region PCR may be a region where various kinds of circuits for controlling a plurality of active pixels PX in the active pixel region APR are formed. For example, the peripheral circuit region PCR may include a plurality of transistors, and the plurality of transistors may be driven to provide a constant signal in each photoelectric conversion region **120** of the active pixel region APR, or to control an output signal from each of the photoelectric conversion region **120**. In an implementation, the transistor may configure various logic circuits, such as a timing generator, a row decoder, a row driver, a correlated double sampler CDS, an analog to digital converter ADC, a latch, a column decoder, and the like.

(22) The pad region PDR may surround the active pixel region APR and the peripheral circuit region PCR. A conductive pad PAD may be on the peripheral region of the semiconductor substrate **110** and may be electrically connected to circuits in the plurality of active pixels PX and the peripheral circuit region PCR. The conductive pad PAD may function as a connection terminal for externally supplying power and signals to a circuit included in the plurality of active pixels PX and the peripheral circuit region PCR.

(23) The semiconductor substrate **110** may include a first surface **110F1** and a second surface **110F2** opposing to each other. Herein, for convenience, the surface of the semiconductor substrate **110** on which a microlens **168** is arranged is referred to as the second surface **110F2**, and the surface opposite to the second surface **110F2** is referred to as the first surface **110F1**.

(24) In an implementation, the semiconductor substrate **110** may include a P-type semiconductor substrate. For example, the semiconductor substrate **110** may be a P-type silicon substrate. In an implementation, the semiconductor substrate **110** may include a P-type bulk substrate and a P-type or a N-type epitaxial layer grown thereon. In an implementation ts, the semiconductor substrate **110** may include an N-type bulk substrate and a P-type or an N-type epitaxial layer grown thereon. In an implementation, the semiconductor substrate **110** may be formed of an organic plastic substrate.

(25) A plurality of active pixels PX may be arranged in a matrix form in the semiconductor substrate **110** in the active pixel region APR. One of the photoelectric conversion regions **120** may be arranged in each of the plurality of active pixels PX. Each of the plurality of photoelectric conversion regions **120** may include a photodiode region **122** and a well region **124**.

(26) A pixel isolation film **130** may be in the semiconductor substrate **110** in the active pixel region APR, and the plurality of active pixels PX may be defined by the pixel isolation film **130**. The pixel isolation film **130** may be between one of the plurality of photoelectric conversion regions **120** and another one of the photoelectric conversion regions **120** adjacent thereto. The one of the photoelectric conversion regions **120** and the other one of the photoelectric conversion regions **120**

adjacent thereto may be physically and electrically separated by the pixel isolation film **130**. The pixel isolation film **130** may be between each of the plurality of photoelectric conversion regions **120** arranged in a matrix form and may have a grid or mesh shape in a plan view.

(27) The pixel isolation film **130** may be in a pixel trench **130T** passing through the semiconductor substrate **110** from the first surface **110F1** to the second surface **110F2** of the semiconductor substrate **110**. The pixel isolation film **130** may include an insulating liner **132** conformally formed on a sidewall of the pixel trench **130T** and a buried conductive layer **134** filled in an inside of the pixel trench **130T** on the insulating liner **132**.

(28) In an implementation, the insulating liner **132** may include a metal oxide, e.g., hafnium oxide, aluminum oxide, tantalum oxide, or the like. In an implementation, the insulating liner **132** may serve as a negative fixed charge layer. In an implementation, the insulating liner **132** may include an insulating material, e.g., silicon oxide, silicon nitride, silicon oxynitride, or the like.

(29) The buried conductive layer **134** may include polysilicon that contains a fining element at a first concentration. The fining element may include, e.g., oxygen, carbon, or fluorine. As used herein, the term “or” is not an exclusive term, e.g., the fining element may include one or more of the enumerated elements. In an implementation, the buried conductive layer **134** may include polysilicon containing oxygen at a concentration of about 5 at % (atomic percent) to about 40 at %. In an implementation, the buried conductive layer **134** may include polysilicon containing oxygen at a concentration of about 20 at % to about 30 at %. In an implementation, the buried conductive layer **134** may include polysilicon containing carbon at a concentration of about 1 at % to about 20 at %. In an implementation, the buried conductive layer **134** may include polysilicon containing fluorine at a concentration of about 1 at % to about 20 at %. In an implementation, the buried conductive layer **134** may include a plurality of grains made of silicon and having a silicon crystal structure, and the fining element may be uniformly dispersed within the grains of silicon. For example, the buried conductive layer **134** may have a diffraction peak at about 28.44° represented by a silicon (**111**) crystal plane in an X-ray diffraction analysis.

(30) The buried conductive layer **134** may include a polysilicon containing the fining element at the first concentration, and the buried conductive layer **134** may have a relatively small grain size. In an implementation, the buried conductive layer **134** may have an average grain size of about 30 nanometers (nm) or less. In an implementation, in the buried conductive layer **134**, a full width at half maximum of an X-ray diffraction peak (the peak being observed at a scattering angle of about 28.44°) by the silicon (**111**) crystal plane observed in the X-ray diffraction analysis may be about 0.4° to about 1.1° (See FIG. 15). In an implementation, the average grain size of the buried conductive layer **134** calculated from the X-ray diffraction peak may be about 7.5 nm to about 20.5 nm.

(31) In an implementation, the pixel trench **130T** may have a first width **w11** at the same level as the first surface **110F1** of the semiconductor substrate **110** and a second width **w12** (that is smaller than the first width **w11**) at the same level as the second surface **110F2** of the semiconductor substrate **110**. For example, the first width **w11** of the pixel trench **130T** measured (e.g., in the first or X direction) at the first surface **110F1** of the semiconductor substrate **110** may be greater than the second width **w12** of the pixel trench **130T** measured at the second surface **110F2** of the semiconductor substrate **110**. In an implementation, the pixel trench **130T** may have a first height **h11** in a direction (e.g., Z direction) perpendicular to the first surface **110F1** of the semiconductor substrate **110**, and a ratio of the first height **h11** to the first width **w11** may be about 20 to about 100.

(32) In an implementation, voids or seams may not be formed within the buried conductive layer **134**. The pixel trench **130T** may have a relatively high aspect ratio (e.g., an aspect ratio of about 20 to 100), and seams could otherwise be formed in the conductive layer **134** in the process of forming the buried conductive layer **134** using polysilicon inside the pixel trench **130T**, and undesired voids could be formed in the buried conductive layer **134** due to grain growth or grain coalescence in the

buried conductive layer **134** in a subsequent heat treatment processes. However, according to the example embodiments, the buried conductive layer **134** may include the polysilicon containing the fining element (e.g., oxygen, carbon, or fluorine), and the buried conductive layer **134** may be formed to have a relatively small grain size in the process of forming the buried conductive layer **134** filling an interior of the pixel trench **130T**. In addition, in a heat treatment process after the formation of the buried conductive layer **134**, the fining element may be able to help restrain grain growth or grain coalescence, which could otherwise occur due to the migration of silicon atoms, thereby voids or seams not being formed in the buried conductive layer **134**. The grain size and microstructure of the buried conductive layer **134** will be described again in detail below with reference to FIG. **15**.

(33) The buried conductive layer **134** may not fill a portion of an interior of the pixel trench **130T** and a bottom surface of the buried conductive layer **134** may be at a level higher than the first surface **110F1** of the semiconductor substrate **110** (e.g., the bottom surface of the buried conductive layer **134** may be inwardly spaced apart from the first surface **110F1** of the semiconductor substrate **110** by a predetermined distance along the vertical direction (Z direction)). A buried insulating layer **140** may fill a remaining portion of the pixel trench **130T** on the bottom surface of the buried conductive layer **134** and the insulating liner **132** may be between the buried insulating layer **140** and an inner wall of the pixel trench **130T**. In an implementation, an upper, lower, or outer surface of the buried insulating layer **140** may be at the same level as (e.g., coplanar with) the first surface **110F1** of the semiconductor substrate **110**. In an implementation, the buried insulating layer **140** may be omitted and the buried conductive layer **134** may be filled in an inside of the pixel trench **130T** through the entire height **h11** of the pixel trench **130T**, such that the bottom or lower surface of the buried conductive layer **134** may be at the same level as (e.g., coplanar with) the first surface **110F1** of the semiconductor substrate **110**.

(34) In an implementation, as shown in FIG. **2**, an isolation film STI (which defines an active region) and a floating diffusion region FD may be on the first surface **110F1** of the semiconductor substrate **110**.

(35) Gate electrodes TG, RG, SG (see FIG. **3**) constituting a part of a plurality of transistors may be on the first surface **110F1** of the semiconductor substrate **110**. In an implementation, the plurality of transistors may include a transmission transistor TX configured to transmit the charge generated in the photoelectric conversion region **120** to the floating diffusion region FD, a reset transistor RX configured to periodically reset the charge stored in the floating diffusion region FD, a drive transistor DX configured to function as a source follower buffer amplifier and to buffer a signal according to the charge charged in the floating diffusion region, and a selection transistor SX for switching and addressing in relation to selecting the active pixel region APR.

(36) In an implementation, as illustrated in FIG. **2**, the transmission gate TG constituting the transmission transistor TX may be a recess gate type extending from the first surface **110F1** of the semiconductor substrate **110** into the semiconductor substrate **110**. In an implementation, a transmission gate insulating layer TGI may be between the semiconductor substrate **110** and the transmission gate TG. For example, as the transmission gate TG is formed in the recess gate type, a portion of the transmission gate insulating layer TGI may extend into the interior of the semiconductor substrate **110**.

(37) A first interconnection structure **152** may be on the first surface **110F1** of the semiconductor substrate **110**. The first interconnection structure **152** may be electrically connected to the gate electrodes or the active region. The first interconnection structure **152** may be formed as a stacked structure of a plurality of layers. The first interconnection structure **152** may include at least one of impurity-doped or undoped polysilicon, metal, metal silicide, metal nitride, or metal-containing film. For example, the first interconnection structure **152** may include tungsten, aluminum, copper, tungsten silicide, titanium silicide, tungsten nitride, titanium nitride, doped polysilicon, and the like.

(38) A first interlayer insulating film **154** may cover the first interconnection structure **152** on the first surface **110F1** of the semiconductor substrate **110**. The first interlayer insulating film **154** may include an insulating material such as silicon oxide, silicon nitride, silicon oxynitride, or the like.

(39) A rear insulating layer **160** may be arranged on the second surface **110F2** of the semiconductor substrate **110**. The rear insulating layer **160** may be arranged on substantially the entire area of the second surface **110F2** of the semiconductor substrate **110**, and the rear insulating layer **160** may contact an upper surface of the pixel isolation film **130** at the same level as the second surface **110F2** of the semiconductor substrate **110**. In an implementation, the rear insulating layer **160** may include a metal oxide such as hafnium oxide, aluminum oxide, tantalum oxide, or the like. In an implementation, the rear insulating layer **160** may include an insulating material such as silicon oxide, silicon nitride, silicon oxynitride, or a low dielectric constant material, or the like.

(40) A guide pattern **162** may be on the rear insulating layer **160**. In a plan view, the guide pattern **162** may have a grid shape or a mesh shape. The guide pattern **162** may help prevent incident light with a tilt angle with respect to one photoelectric conversion region **120**, from entering the photoelectric conversion region **120**. The guide pattern **162** may include at least one metallic material, e.g., tungsten, aluminum, titanium, ruthenium, cobalt, nickel, copper, gold, silver or platinum.

(41) A passivation layer **164** may cover the rear insulating layer **160** and the guide pattern **162** on the second surface **110F2** of the semiconductor substrate **110**. A color filter **166** and a microlens **168** may be on the passivation layer **164**.

(42) In an implementation, a supporting substrate **170** may be on the first surface **110F1** of the semiconductor substrate **110**. An adhesive member may be further arranged between the supporting substrate **170** and the first interlayer insulating film **154**.

(43) In the process of forming the buried conductive layer **134** using polysilicon inside the pixel trench **130T** having a relatively high aspect ratio, it is possible that a seam could be formed in the buried conductive layer **134**, and in a subsequent heat treatment process grain growth or grain coalescence could occur to form an undesired void in the buried conductive layer **134**. If such a void were to be formed, performance of the image sensor **100** may be lowered, due to an occurrence of a dark current or an increase in noise level, or the like.

(44) On the other hand, in the image sensor **100** according to an embodiment, the buried conductive layer **134** may include polysilicon containing the fining element (e.g., oxygen, carbon, or fluorine), and the buried conductive layer **134** may be formed to have a relatively small grain size. In addition, the fining element may help prevent grain growth or grain coalescence in the heat treatment process after the formation of the buried conductive layer **134**, and the formation of undesired voids may be prevented. For example, voids or seams may not be formed in the buried conductive layer **134**, and the image sensor **100** may be prevented from generating a dark current or increasing of noise level to have improved performance.

(45) FIG. **15** illustrates an X-ray diffraction analysis graph of the buried conductive layer included in the image sensors according to an Example and Comparative Examples.

(46) The following Example and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Example and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Example and Comparative Examples.

(47) Referring to FIG. **15**, a buried conductive layer EX**11** according to an Example was formed using polysilicon containing oxygen as the fining element at a first concentration, as described with reference to FIGS. **1** and **2**, and then a subsequent heat treatment was performed. Buried conductive layers CO**11** and CO**12** according to Comparative Examples 1 and 2, respectively, were formed using polysilicon without the fining element, and then a subsequent heat treatment was performed.

(48) Referring to FIG. 15 and the following Table 1, in the buried conductive layer EX11 according to the Example and the buried conductive layers CO11 and CO12 according to the Comparative Examples, diffraction peaks by silicon (111) crystal planes are observed at a scattering angle of about 28.44°, and the intensity of the diffraction peak of the buried conductive layer EX11 according to the Example was lower than the intensity of the diffraction peaks of the buried conductive layers CO11 and CO12 according to the Comparative Examples.

(49) In addition, a full width at half maximum (FEX11) by the silicon (111) crystal plane of the buried conductive layer EX11 according to the Example was higher than a full width at half maximum FCO11 of the buried conductive layer CO11 according to Comparative Example 1 and a full width at half maximum FCO12 of the buried conductive layer CO12 according to Comparative Example 2. From the calculation based on the full widths at half maximum of such X-ray diffraction peaks, the buried conductive layer EX11 according to the Example may have an average grain size of about 16.8 nm, while the buried conductive layer CO11 according to the Comparative Example 1 may have an average grain size of about 43.5 nm, and the buried conductive layer CO12 according to the Comparative Example 2 may have an average grain size of about 45.8 nm.

(50) TABLE-US-00001 TABLE 1 Intensity of (111) plane Full width at diffraction peak half maximum Comparative Example 1 481 0.19 (CO11) Comparative Example 2 611 0.18 (CO12) Example (EX11) 79 0.49

(51) Voids or seams were observed inside the buried conductive layers CO11 and CO12 according to the Comparative Examples, while voids or seams were not observed inside the buried conductive layer EX11 according to the Example.

(52) According to an embodiment, the buried conductive layer 134 (see FIG. 2) may have a relatively small grain size by including the fining element (including at least one of oxygen, carbon, and fluorine), and then the formation of undesired voids in a subsequent heat treatment process may be prevented by the fining element.

(53) FIG. 3 illustrates an equivalent circuit diagram of the active pixel PX of the image sensor 100 of FIGS. 1 and 2 according to example embodiments.

(54) Referring to FIG. 3, the plurality of active pixels PX may be arranged in a matrix form. Each of the plurality of active pixels PX may include a transmission transistor TX and logic transistors RX, SX, DX. Herein, the logic transistors may include a reset transistor RX, a selection transistor SX, and a drive transistor DX (or a source follower transistor). The reset transistor RX may include a reset gate RG and the selection transistor SX may include a selection gate SG and the transfer transistor TX may include a transmission gate TG.

(55) Each of the plurality of active pixels PX may further include a photoelectric conversion device PD and a floating diffusion region FD. The photoelectric conversion device PD may correspond to the photoelectric conversion region 120 described with reference to FIGS. 1 and 2. The photoelectric conversion device PD may generate and accumulate photo charges in proportion to the amount of incident light from an outside, and a photodiode, a photo transistor, a photo gate, a pinned photodiode PPD and combinations thereof may be used as the photoelectric conversion device PD.

(56) The transmission gate TG may transfer the charges generated in the photoelectric conversion device PD to the floating diffusion region FD. The floating diffusion region FD may receive the charges generated in the photoelectric conversion device PD and accumulate the charges. The drive transistor DX may be controlled according to the amount of the photo charges accumulated in the floating diffusion region FD.

(57) The reset transistor RX may periodically reset the charges accumulated in the floating diffusion region FD. A drain electrode of the reset transistor RX is connected to the floating diffusion region FD and a source electrode thereof is connected to a power source voltage VDD. When the reset transistor RX is turned on, the power source voltage VDD connected to the source electrode of the reset transistor RX is transferred to the floating diffusion region FD. When the

reset transistor RX is turned on, the charges accumulated in the floating diffusion region FD are discharged to reset the floating diffusion region FD.

(58) The drive transistor DX is connected to a current source (not shown) located outside the plurality of active pixels PX and then functions as a source follower buffer amplifier, and it amplifies potential change in the floating diffusion region FD and outputs it to the output line VOUT.

(59) The selection transistor SX may select the plurality of active pixels PX row by row and when the selection transistor SX is turned on, the power supply voltage VDD may be transferred to a source electrode of the drive transistor DX.

(60) FIG. 4 illustrates a cross-sectional view of an image sensor **100A** according to example embodiments. FIG. 4 is a cross-sectional view of a portion corresponding to the portion II-II' of FIG. 1. In FIG. 4, the same reference numerals as in FIGS. 1 to 3 denote the same elements.

(61) Referring to FIG. 4, the pixel isolation layer **130A** may include an insulating liner **132** and a buried conductive layer **134A**. The buried conductive layer **134A** may contain polysilicon containing the fining element at the first concentration and a P-type dopant at a second concentration or an N-type dopant at the second concentration. For example, the fining element may include oxygen, carbon, or fluorine. In an implementation, the P-type dopant may include, e.g., boron, aluminum, or indium. In an implementation, the N-type dopant may include, e.g., phosphorus, arsenic, or antimony. The fining element may function as an additive, with which the buried conductive layer **134A** may be formed to have a fine grain size, and the P type dopant or the N type dopant may help increase the conductivity of the buried conductive layer **134A**.

(62) In an implementation, the fining elements may be uniformly dispersed in the buried conductive layer **134A**, and the P-type dopant or the N-type dopant may also be uniformly dispersed in the buried conductive layer **134A**.

(63) In the manufacturing process of the image sensor **100A** according to an embodiment, a first conductive layer **134A1** (see FIG. 9A) may be formed by using polysilicon containing the P-type dopant or the N-type dopant on an inner wall of the pixel trench **130T**, a second conductive layer **134B1** (see FIG. 9B) may be formed on the first conductive layer **134A1** by using the polysilicon containing the fining element, and the buried conductive layer **134A** may be formed by performing a heat treatment process and then diffusing the fining element in the first conductive layer **134A1** and the P-type or the N-type dopant in the second conductive layer **134B1**.

(64) FIG. 5 illustrates a cross-sectional view of an image sensor **100B** according to example embodiments. FIG. 5 is a cross-sectional view taken along line II-II' of FIG. 1. In FIG. 5, the same reference numerals as in FIGS. 1 to 4 denote the same elements.

(65) Referring to FIG. 5, a pixel isolation film **130B** may include an insulating liner **132**, a buried conductive layer **134B**, and an interface layer **136B**. The buried conductive layer **134B** may include polysilicon containing the fining element at a first concentration, and the fining element may include at least one of oxygen, carbon, and fluorine.

(66) The interface layer **136B** may be between the insulating liner **132** and the buried conductive layer **134B**. The interface layer **136B** may include polysilicon containing the P-type dopant or the N-type dopant.

(67) In an implementation, the interface layer **136B** may be between the rear insulating layer **160** and the buried conductive layer **134B** at the same level as the second surface **110F2** of the semiconductor substrate **110**, so that the buried conductive layer **134B** may not contact the rear insulating layer **160**. In an implementation, the interface layer **136B** may surround the sidewall of the buried conductive layer **134B** on the sidewall of the pixel trench **130T**, so that both the buried conductive layer **134B** and the interface layer **136B** may be in contact with the rear insulating layer **160** at the same level as the second surface **110F2** of the semiconductor substrate **110**.

(68) In the manufacturing process of the image sensor **100B** according to the example embodiments, the first conductive layer **134A1** (see FIG. 9A) may be formed on the inner wall of the

pixel trench **130T** by using polysilicon containing the P-type dopant or the N-type dopant, and then a second conductive layer **134B1** (see FIG. 9B) may be formed on the first conductive layer **134A1** by using polysilicon containing the fining element. Herein, a part of the first conductive layer **134A1** may correspond to the interface layer **136B** and a part of the second conductive layer **134B1** may correspond to the buried conductive layer **134B**, respectively.

(69) FIG. 6 illustrates a cross-sectional view of an image sensor **100C** according to example embodiments. FIG. 6 is a cross-sectional view of a portion corresponding to the portion II-II' of FIG. 1. In FIG. 6, the same reference numerals as in FIGS. 1 to 5 denote the same elements.

(70) Referring to FIG. 6, a pixel isolation film **130C** may include an insulating liner **132**, a buried conductive layer **134C**, and an interface layer **136C**. The buried conductive layer **134C** may include polysilicon containing the fining element at a first concentration, and the fining element may include at least one of oxygen, carbon, and fluorine.

(71) The interface layer **136C** may be between the insulating liner **132** and the buried conductive layer **134C**, and may have a tapered shape in a direction (e.g., Z direction) toward a first surface **110F1** of the semiconductor substrate **110**. For example, a width of the interface layer **136C** may become smaller in the Z direction from the second surface **110F2** to the first surface **110F1** of the semiconductor substrate **110**. The interface layer **136C** may include polysilicon containing a P-type dopant or an N-type dopant.

(72) In the manufacturing process of the image sensor **100C** according to the example embodiments, a first conductive layer **134A2** (see FIG. 12A) may be formed on an inner wall of the pixel trench **130T** by using polysilicon containing the P-type dopant or the N-type dopant. And then, by performing anisotropic etching to the first conductive layer **134A2**, a top portion **134A2T** of the first conductive layer **134A2** (see FIG. 12B) may have the tapered shape while a top entrance of the pixel trench **130T** may be expanded. Thereafter, a second conductive layer **134B2** (see FIG. 12C) may be formed on the first conductive layer **134A2** using polysilicon containing the fining element. Herein, a part of the first conductive layer **134A2** may correspond to the interface layer **136C** and a part of the second conductive layer **134B2** may correspond to the buried conductive layer **134C**, respectively.

(73) FIGS. 7A-7L illustrate cross-sectional views of stages in a method of manufacturing the image sensor **100** in accordance with example embodiments. In FIGS. 7A-7L, cross-sectional views corresponding to the cross-sectional views taken along line II-II' of FIG. 1 are shown in the order of process. In FIGS. 7A-7L, the same reference numerals as in FIGS. 1-6 denote the same elements.

(74) Referring to FIG. 7A, the semiconductor substrate **110** having the first surface **110F1** and the second surface **110F2** opposite to each other is provided.

(75) Thereafter, a first mask layer **210** having an opening **210H** may be formed on the first surface **110F1** of the semiconductor substrate **110** and using the first mask layer **210**, a part of the semiconductor substrate **110** may be removed from the first surface **110F1** to form an isolation trench ST.

(76) Referring to FIG. 7B, an isolation insulating layer **220** may be formed on the first surface **110F1** of the semiconductor substrate **110** and the first mask layer **210** to fill the isolation trench ST. The isolation insulating layer **220** may be formed using silicon oxide, silicon oxynitride, or silicon nitride.

(77) Thereafter, a mask pattern may be formed on the isolation insulating layer **220**, and the pixel trench **130T** may be formed in the semiconductor substrate **110** using the mask pattern.

(78) The pixel trench **130T** may have a first height **h01** from the first surface **110F1** of the semiconductor substrate **110** and may have a first width **w11** along a first direction (an X direction) at the same level as the first surface **110F1** of the semiconductor substrate **110**. In an implementation, the pixel trench **130T** may have an aspect ratio of about 20 to about 100.

(79) In an implementation, the pixel trench **130T** may have a second width **w13** (that is less than

the first width **w11** along the first direction (the X direction)) at a bottom portion **130TB** of the pixel trench **130T**. In this case, a sidewall **130TS** of the pixel trench **130T** may be slightly inclined so that the width of the pixel trench **130T** becomes narrower from the top to the bottom of the pixel trench **130T**.

(80) Referring to FIG. 7C, a preliminary insulating liner **132P** may be conformally formed on the isolation insulating layer **220** and the inner wall of the pixel trench **130T** by a chemical vapor deposition (CVD) process, or an atomic layer deposition (ALD) process. The preliminary insulating liner **132P** may have substantially the same thickness on the sidewall **130TS** and the bottom portion **130TB** of the pixel trench **130T**.

(81) Referring to FIG. 7D, a conductive layer **134P** filling the inner of the pixel trench **130T** may be formed on the preliminary insulating liner **132P**. The conductive layer **134P** may include polysilicon containing the fining element at a first concentration.

(82) In an implementation, the process of forming the conductive layer **134P** may include the CVD process or the ALD process using a silicon source material and the fining element source material as precursors. In an implementation, when the fining element includes oxygen, the fining element source material may include, e.g., an oxidizing agent such as nitrogen oxide (N.sub.2O) or nitrogen monoxide (NO). In an implementation, when the fining element includes carbon, the fining element source material may include, e.g., hydrocarbons such as methane (CH.sub.4), ethylene (C.sub.2H.sub.4), acetylene (C.sub.2H.sub.2) or propane (C.sub.3H.sub.8). In an implementation, when the fining element includes fluorine, the fining element source material may include, e.g., a fluorine-containing precursor material such as nitrogen trifluoride (NF.sub.3), silicon tetrafluoride (SiF.sub.4), etc. . . .

(83) For example, the conductive layer **134P** may be formed by reaction according to the following Formula 1 using a silicon source material and an oxygen source material.

$$\text{SiH.sub.4 (g)} + \text{N.sub.2O.fwdarw.Si (s)} + \text{O} + 2\text{H.sub.2 (g)} + \text{N.sub.2 (g)} \quad \text{Formula 1}$$

(84) In an implementation, the conductive layer **134P** may include polysilicon containing about 5 at % to 40 at % of oxygen. In an implementation, when the fining element includes carbon or fluorine, the conductive layer **134P** may include polysilicon containing about 1 at % to 20 at % of carbon or polysilicon containing about 1 at % to 20 at % of fluorine.

(85) The conductive layer **134P** may be formed to include polysilicon containing the fining element at the first concentration, and the conductive layer **134P** may have a relatively small grain size. For example, the conductive layer **134P** may have polycrystalline microstructure having an average grain size of less than about 30 nm. In an implementation, voids or seams may not be formed within the conductive layer **134P** in the pixel trench **134T** having a relatively large aspect ratio.

(86) Referring to FIG. 7E, a portion of the conductive layer **134P** (see FIG. 7D) on the preliminary insulating liner **132P** outside the pixel trench **134T** may be removed to remain the buried conductive layer **134** in the pixel trench **134T**. In an implementation, as shown in FIG. 7E, the top surface of the buried conductive layer **134** may be at a lower level than the first surface **110F1** of the semiconductor substrate **110**.

(87) Referring to FIG. 7F, a preliminary buried insulating layer **140P** may be formed on the buried conductive layer **134** and the preliminary insulating liner **132P** using an insulating material. The preliminary buried insulating layer **140P** may fill the remaining space of the pixel trench **130T**.

(88) Referring to FIG. 7G, a portion of the preliminary buried insulating layer **140P** (see FIG. 7F), a portion of the preliminary insulating liner **132P** (see FIG. 7F), a portion of the isolation insulating layer **220** and the first mask layer **210** (see FIG. 7F) may be removed to expose the first surface **110F1** of the semiconductor substrate **110**. A remaining portion of the preliminary buried insulating layer **140P** may be the buried insulating layer **140**, a remaining portion of the preliminary insulating liner **132P** may be the insulating liner **132** and a remaining portion of the isolation insulating layer **220** may be the isolation film STI.

(89) Referring to FIG. 7H, a photoelectric conversion region **120** including a photodiode region

122 and a well region **124** may be formed from or at the first surface **110F1** of the semiconductor substrate **110** by an ion implantation process. For example, the photodiode region **122** may be formed by doping with N-type impurities, and the well region **124** may be formed by doping with P-type impurities.

(90) A gate structure including a transmission gate TG and a transmission gate insulating layer TGI may be formed on the first surface **110F1** of the semiconductor substrate **110** and then a floating diffusion region FD and an active region may be formed in a part of the first surface **110F1** of the semiconductor substrate **110** by the ion implantation process.

(91) Referring to FIG. 7I, a first interconnection structure **152** and a first interlayer insulating film **154** covering the first interconnection structure **152** may be formed on the semiconductor substrate **110** by repeatedly performing the operations of forming a conductive layer on the first surface **110F1** of the semiconductor substrate **110**, patterning the conductive layer, and forming an insulating layer covering the patterned conductive layer.

(92) Thereafter, a supporting substrate **170** may be adhered to the first interlayer insulating film **154**. An adhesive layer may be between the supporting substrate **170** and the first interlayer insulating film **154**.

(93) Referring to FIG. 7J, the semiconductor substrate **110** may be inverted such that the second surface **110F2** of the semiconductor substrate **110** faces upward. Herein, the bottom portion **130TB** of the pixel trench **130T** may not be exposed at the second surface **110F2**.

(94) Referring to FIG. 7K, a portion of the semiconductor substrate **110** may be removed from or at the second surface **110F2** of the semiconductor substrate **110** by a planarization process such as a CMP process or an etch-back process until the buried conductive layer **134** is exposed. As the removal process is performed, the level of the second surface **110F2** of the semiconductor substrate **110** may be lowered.

(95) One active pixel PX surrounded by the pixel isolation film **130** may be physically and electrically separated from the active pixel PX adjacent thereto. The pixel trench **130T** extends from the first surface **110F1** to the second surface **110F2** of the semiconductor substrate **110** and may have a first height **h11** along the vertical direction, the Z direction. In an implementation, the first height **h11** of the pixel trench **130T** after the planarization process may be smaller than the first height **h01** (see FIG. 7B) of the pixel trench **130T** prior to the planarization process. In an implementation, the first height **h11** of the pixel trench **130T** after the planarization process may be substantially identical to the first height **h01** of the pixel trench **130T** before the planarization process.

(96) Thereafter, a rear insulating layer **160** may be formed on the second surface **110F2** of the semiconductor substrate **110**, the buried conductive layer **134**, and the insulating liner **132**. The rear insulating layer **160** may be formed using an insulating material such as a metal oxide such as hafnium oxide, aluminum oxide, tantalum oxide, or the like, silicon oxide, silicon nitride, silicon oxynitride, or a low-k material.

(97) Referring to FIG. 7L, a conductive layer may be formed on the rear insulating layer **160**, and the conductive layer may be patterned to form a guide pattern **162**. The guide pattern **162** may overlap the pixel isolation film **130** in the active pixel region APR.

(98) Thereafter, a conductive pad PAD (see FIG. 1) may be formed on the rear insulating layer **160** in the pad region PDR. The conductive pad PAD may be formed by sequentially forming a first metal layer and a second metal layer. For example, the first metal layer may be formed using the metal material such as titanium, titanium nitride, tantalum, tantalum nitride, titanium tungsten, tungsten, aluminum, cobalt, nickel or copper by a CVD process, an ALD process or the like. The second metal layer may be formed using the metal material such as tungsten, aluminum, cobalt, nickel, or copper by a CVD process, an ALD process, a plating process, or the like.

(99) Thereafter, a passivation layer **164** may be formed on the rear insulating layer **160** and the guide pattern **162** and a color filter **166** and a microlens **168** may be formed on the passivation

layer **164**.

(100) The image sensor **100** may be completed by the above-described process.

(101) According to the method of manufacturing the image sensor according to the above-described example embodiments, the buried conductive layer **134** may be formed using polysilicon containing the fining element, and voids or seams may not be formed in the buried conductive layer **134**. Further, even though the heat treatment process is further performed, the fining element included in the buried conductive layer **134** may suppress the movement of silicon atoms or inhibit grain growth, and therefore the formation of voids or seams may be prevented inside the buried conductive layer **134**.

(102) FIG. **8** illustrates a flowchart of a method of manufacturing the image sensor **100** according to the example embodiments. FIGS. **9A** to **9C** illustrate cross-sectional views of stages in a method of manufacturing the image sensor **100** according to the example embodiments. FIG. **8** and FIGS. **9A** to **9C**, the same reference numerals as in FIGS. **1** to **7L** denote the same elements.

(103) First, the process described with reference to FIGS. **7A** to **7C** may be performed to form a preliminary insulating liner **132P** inside the pixel trench **130T**.

(104) Referring to FIGS. **8** and **9A**, a first conductive layer **134A1** including polysilicon may be formed on an inner wall of the pixel trench **130T** (operation **S210**). The first conductive layer **134A1** may include polysilicon that is free of impurities or fining elements.

(105) In an implementation, the first conductive layer **134A1** may be formed by a reaction according to the following Formula 2 using a silicon source material.

$\text{SiH.sub.4 (g).fwdarw.Si (s)+2H.sub.2 (g)}$ Formula 2

(106) Referring to FIGS. **8** and **9B**, a second conductive layer **134B1** including polysilicon containing fining elements may be formed on the first conductive layer **134A1** to fill an interior of the pixel trench **130T** (operation **S220**).

(107) In an implementation, when the fining element includes oxygen, the second conductive layer **134B1** may be formed using a silicon source material and an oxygen source material by the reaction according to Formula 1 below.

$\text{SiH.sub.4 (g)+N.sub.2O.fwdarw.Si (s)+O+2H.sub.2 (g)+N.sub.2 (g)}$ Formula 1

(108) Referring to FIGS. **8** and **9C**, the semiconductor substrate **110** may be heat-treated, e.g., annealed (operation **S230**). The fining element contained in the second conductive layer **134B1** may be diffused into the first conductive layer **134A1** by the heat treatment process, to thereby form a conductive layer **134P1**.

(109) In an implementation, the process for forming the first conductive layer **134A1** and the process for forming the second conductive layer **134B1** may be performed in-situ within the same chamber or reactor. In an implementation, the process for forming the first conductive layer **134A1** and the process for forming the second conductive layer **134B1** may be performed ex-situ in different chambers or reactors.

(110) In an implementation, as illustrated in FIGS. **8** and **9A** to **9C**, the second conductive layer **134B1** may be formed to fill the pixel trench **130T**. In an implementation, the first conductive layer **134A1** and the second conductive layer **134B1** having a relatively thin thickness may be alternately and repeatedly formed on the inner wall of the pixel trench **130T**. For example, the processes of forming the first conductive layer **134A1** and the second conductive layer **134B1** may be repeated *n* times to fill the inside of the pixel trench **130T**.

(111) Thereafter, the image sensor **100** may be completed by performing the processes described with reference to FIGS. **7E** to **7L**.

(112) FIG. **10** illustrates a flowchart of a method of manufacturing the image sensor **100** according to the example embodiments.

(113) Referring to FIG. **10** together with FIG. **9A**, a first conductive layer **134A1** containing polysilicon containing fining elements may be formed on the inner wall of the pixel trench **130T** (operation **S210A**).

(114) Referring to FIG. 10 together with FIG. 9B, a second conductive layer **134B1** including polysilicon not containing the fining elements or impurities may be formed on the first conductive layer **134A1** to fill the inside of the pixel trench **130T** (operation **S220A**).

(115) Referring to FIG. 10 together with FIG. 9C, the semiconductor substrate **110** may be heat-treated (operation **S230A**). The fining elements included in the first conductive layer **134A1** may be diffused into the second conductive layer **134B1** by the heat treatment process to form the conductive layer **134P1**.

(116) FIG. 11 illustrates a flowchart of stages in a method of manufacturing the image sensor **100** according to the example embodiments. FIGS. 12A to 12D illustrate cross-sectional views of stages in a method of manufacturing the image sensor **100** according to example embodiments.

(117) First, the process described with reference to FIGS. 7A to 7C is performed to form a preliminary insulating liner **132P** inside the pixel trench **130T**.

(118) Referring to FIGS. 11 and 12A, a first conductive layer **134A2** including polysilicon may be formed on an inner wall of the pixel trench **130T** (operation **S210B**). The first conductive layer **134A2** may include polysilicon that is free of impurities or fining elements.

(119) Referring to FIGS. 11 and 12B, an anisotropic etching process may be performed on the first conductive layer **134A2** (operation **S215B**). A portion of the first conductive layer **134A2** on the preliminary insulating liner **132P** on the first surface **110F1** of the semiconductor substrate **110** and a portion of the first conductive layer **134A2** on the bottom portion **130TB** of the pixel trench **130T** may be removed by the anisotropic etching process. The first conductive layer **134A2** may remain on a sidewall **130TS** of the pixel trench **130T** and a top portion **134A2T** of the first conductive layer **134A2** may remain and may have a tapered shape in a direction (Z direction) toward the first surface **110F1** of the semiconductor substrate **110** (e.g., in the direction toward an entrance of the pixel trench **130T**). As the top portion **134A2T** of the first conductive layer **134A2** has a tapered shape, the entrance of the pixel trench **130T** may expand laterally as compared to the bottom of the pixel trench **130T**.

(120) Referring to FIGS. 11 and 12C, a second conductive layer **134B2** including polysilicon containing the fining elements may be formed on the first conductive layer **134A2** to fill the inside of the pixel trench **130T** (operation **S220B**).

(121) As the entrance of the pixel trench **130T** expands laterally as compared to the bottom of the pixel trench **130T**, the source material may be smoothly supplied to the inside of the pixel trench **130T** in the process of forming the second conductive layer **134B2**. Thus, the second conductive layer **134B2** may densely fill the inside of the pixel trench **130T** without voids or seams.

(122) Referring to FIGS. 11 and 12D, the semiconductor substrate **110** may be heat-treated, e.g., annealed (operation **S230B**). The fining elements included in the second conductive layer **134B2** may be diffused into the first conductive layer **134A2** by the heat treatment process to form the conductive layer **134P2**.

(123) In an implementation, the process for forming the first conductive layer **134A2**, the process for anisotropically etching the first conductive layer **134A2**, and the process for forming the second conductive layer **134B2** may be performed in-situ in a same chamber or reactor. In an implementation, the process for forming the first conductive layer **134A2**, the process for anisotropically etching the first conductive layer **134A2**, and the process for forming the second conductive layer **134B2** may be performed ex-situ in different chambers or reactors.

(124) In an implementation, as illustrated in FIGS. 11 and 12A to 12D, the second conductive layer **134B2** may include polysilicon containing the fining elements. In an implementation, the first conductive layer **134A2** may include polysilicon containing the fining elements and the second conductive layer **134B2** may include polysilicon that does not contain the fining elements or impurities.

(125) In an implementation, as illustrated in FIGS. 11 and 12A to 12D, the second conductive layer **134B2** may fill the pixel trench **130T**. In an implementation, on the inner wall of the pixel trench

130T, the first conductive layer **134A2** and the second conductive layer **134B2** having a relatively thin thickness may be alternately and repeatedly formed. For example, the process of forming the first conductive layer **134A2**, the anisotropic etching process of the first conductive layer **134A2**, the process of forming the second conductive layer **134B2**, and the anisotropic etching process of the second conductive layer **134B2** are repeated n times, and finally, the first conductive layer **134A2** may be formed to fill the inside of the pixel trench **130T**.

(126) Thereafter, the image sensor **100** may be completed by performing the processes described with reference to FIGS. 7E to 7L.

(127) FIG. 13 illustrates a flowchart of a method of manufacturing the image sensor **100A** according to the example embodiments.

(128) Referring to FIG. 13 together with FIG. 9A, a first conductive layer **134A1** including polysilicon containing dopant at a second concentration may be formed on the inner wall of the pixel trench **130T** (operation S210C). The dopant may include the N-type dopant or the P-type dopant.

(129) In an implementation, the first conductive layer **134A1** may be formed by reactions according to Formula 3 or Formula 4 using the silicon source material and the dopant source material.

$\text{SiH.sub.4(g)} + \text{PH.sub.3.fwdarw.Si(s)} + \text{P} + \text{H.sub.2(g)}$ Formula 3

$\text{SiH.sub.4(g)} + \text{BCl.sub.3.fwdarw.Si(s)} + \text{B} + \text{H.sub.2(g)} + \text{Cl.sub.2(g)}$ Formula 4

(130) Referring to FIG. 13 together with FIG. 9B, a second conductive layer **134B1** including polysilicon containing fining elements at the first concentration may be formed on the first conductive layer **134A1**, to thereby fill the inside of the pixel trench **130T** (operation S220C).

(131) Referring to FIG. 13 together with FIG. 9C, the semiconductor substrate **110** may be heat-treated (operation S230C). The dopant contained in the first conductive layer **134A1** may be diffused into the second conductive layer **134B1** by the heat treatment process and the fining elements contained in the second conductive layer **134B1** may be diffused into the first conductive layer **134A1**, so that the conductive layer **134P1** may be formed.

(132) Thereafter, the image sensor **100A** including the buried conductive layer **134A** may be completed by performing the processes described with reference to FIGS. 7E to 7L.

(133) In an implementation, as illustrated in FIG. 13, the dopant and the fining elements may be uniformly dispersed in the entire region of the buried conductive layer **134A** by performing the heat treatment process. In an implementation, the heat treatment process of the semiconductor substrate **110** may be omitted and the first conductive layer **134A1** portion may be remained as the interface layer **136B** and the second conductive layer **134B1** portion may be remained as the buried conductive layer **134B**. In this case, the image sensor **100B** described with reference to FIG. 5 may be formed.

(134) FIG. 14 illustrates a flowchart of a method of manufacturing the image sensor **100A** according to the example embodiments.

(135) Referring to FIG. 14 together with FIG. 12A, a first conductive layer **134A2** including polysilicon containing dopants at the second concentration may be formed on the inner wall of the pixel trench **130T** (operation S210D). The dopant may include the N-type dopant or the P-type dopant.

(136) Referring to FIG. 14 together with FIG. 12B, an anisotropic etching process may be performed on the first conductive layer **134A2** (operation S215D). The first conductive layer **134A2** may remain on the sidewall **130TS** of the pixel trench **130T** by the anisotropic etching process and the entrance of the pixel trench **130T** may be further expanded laterally as compared to the bottom of the pixel trench **130T**.

(137) Referring to FIG. 14 together with FIG. 12C, a second conductive layer **134B2** including polysilicon containing fining elements at a first concentration may be formed on the first conductive layer **134A2** to thereby fill the inside of the pixel trench **130T** (operation S220D).

(138) Referring to FIG. 14 together with FIG. 12D, the semiconductor substrate **110** may be heat-treated (operation S230D). The dopants contained in the first conductive layer **134A2** may be diffused into the second conductive layer **134B2** by the heat treatment process and the fining elements contained in the second conductive layer **134B2** may be diffused into the first conductive layer **134A2**, so that the conductive layer **134P2** may be formed.

(139) Thereafter, the image sensor **100A** including the buried conductive layer **134A** may be completed by performing the processes described with reference to FIGS. 7E to 7L.

(140) In an implementation, as illustrated in FIG. 14, the dopants and the fining elements may be uniformly dispersed in the entire region of the buried conductive layer **134A** by performing the heat treatment process. In an implementation, the heat treatment process of the semiconductor substrate **110** may be omitted and the portion of the first conductive layer **134A2** may be remained as the interface layer **136C** and the portion of the second conductive layer **134B2** may remain as the buried conductive layer **134C**. In this case, the image sensor **100C** described with reference to FIG. 6 may be formed.

(141) By way of summation and review, as a degree of integration of the image sensor increases, a size of each of the plurality of photodiode regions may be reduced. A degree of difficulty of a process for forming the pixel isolation region may increase.

(142) One or more embodiments may provide an image sensor including a photodiode.

(143) One or more embodiments may provide an image sensor that may fill a buried conductive layer without voids or seams in a pixel isolation region having a large aspect ratio.

(144) Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

Claims

1. An image sensor, comprising: a semiconductor substrate having a first surface and a second surface opposite the first surface; a transmission gate on the first surface of the semiconductor substrate; and a pixel isolation film in a pixel trench penetrating through the semiconductor substrate, the pixel isolation film defining active pixels in the semiconductor substrate, wherein the pixel isolation film includes: an insulating liner on an inner wall of the pixel trench; a buried layer on the insulating liner and filling a portion of the pixel trench; and a buried insulating layer disposed in a remaining portion of the pixel trench, and wherein the buried layer includes a first end being close to the first surface, the first end being spaced apart from the first surface in a first direction perpendicular to the first surface.
2. The image sensor as claimed in claim 1, wherein the insulating liner includes at least one of metal oxide, silicon oxide, or silicon nitride.
3. The image sensor as claimed in claim 1, wherein the insulating liner includes at least one of hafnium oxide, aluminum oxide, or tantalum oxide.
4. The image sensor as claimed in claim 1, wherein the pixel trench extends from the first surface of the semiconductor substrate to the second surface of the semiconductor substrate.
5. The image sensor as claimed in claim 1, wherein the insulating liner is in contact with the semiconductor substrate.
6. The image sensor as claimed in claim 1, wherein: the insulating liner is disposed between the

buried layer and the semiconductor substrate, and the buried layer is not in contact with the semiconductor substrate.

7. The image sensor as claimed in claim 1, wherein: the first end of the buried layer has a first width in a second direction parallel to the first surface of the semiconductor substrate, the buried insulating layer has a second width in the second direction, and the second width is greater than the first width.

8. The image sensor as claimed in claim 1, wherein a bottom surface of the buried insulating layer is coplanar with the first surface of the semiconductor substrate.

9. The image sensor as claimed in claim 1, wherein the buried insulating layer is in contact with the first surface of the semiconductor substrate.

10. The image sensor as claimed in claim 1, further comprising: an interconnection structure on the first surface of the semiconductor substrate; and a microlens on the second surface of the semiconductor substrate, wherein the pixel isolation film extends from the first surface to the second surface of the semiconductor substrate and passes through the semiconductor substrate.

11. The image sensor as claimed in claim 1, further comprising: a rear insulating layer disposed on the second surface of the semiconductor substrate; and a guide pattern on the rear insulating layer, the guide pattern being at a position vertically overlapping the pixel isolation film.

12. The image sensor as claimed in claim 11, wherein: the pixel isolation film includes a first end and a second end, the first end is disposed adjacent to the first surface of the semiconductor substrate, the second end is disposed adjacent to the second surface of the semiconductor substrate, and at the second end of the pixel isolation film, a top surface of the insulating liner is in contact with the rear insulating layer.

13. The image sensor as claimed in claim 1, wherein the pixel trench has a first width at a same level as the first surface of the semiconductor substrate and a second width that is smaller than the first width at a same level as the second surface.

14. The image sensor as claimed in claim 13, wherein a ratio of a first height in a direction perpendicular to the first surface with respect to the first width is about 20 to about 100.

15. An image sensor, comprising: a semiconductor substrate having a first surface and a second surface opposite the first surface; a transmission gate on the first surface of the semiconductor substrate; and a pixel isolation film in a pixel trench, the pixel trench penetrating through the semiconductor substrate, the pixel isolation film defining active pixels in the semiconductor substrate, wherein the pixel isolation film includes: an insulating liner on an inner wall of the pixel trench; a buried layer on the insulating liner and filling a portion of the pixel trench; and a buried insulating layer disposed in a remaining portion of the pixel trench, and wherein the buried insulating layer is disposed adjacent to the first surface of the semiconductor substrate and the buried insulating layer vertically overlaps the buried layer.

16. The image sensor as claimed in claim 15, wherein: the pixel trench extends from the first surface of the semiconductor substrate to the second surface of the semiconductor substrate, the insulating liner is in contact with the semiconductor substrate, the insulating liner is disposed between the buried layer and the semiconductor substrate, and the buried layer is not in contact with the semiconductor substrate.

17. The image sensor as claimed in claim 15, wherein the buried insulating layer is in contact with the first surface of the semiconductor substrate.

18. The image sensor as claimed in claim 15, further comprising: a rear insulating layer disposed on the second surface of the semiconductor substrate; and a guide pattern on the rear insulating layer, the guide pattern being at a position vertically overlapping the pixel isolation film.

19. The image sensor as claimed in claim 18, wherein: the pixel isolation film includes a first end and a second end, the first end is disposed adjacent to the first surface of the semiconductor substrate, the second end is disposed adjacent to the second surface of the semiconductor substrate, and at the second end of the pixel isolation film, a top surface of the insulating liner is in contact

with the rear insulating layer.

20. The image sensor as claimed in claim 19, wherein: the buried layer includes a first end being close to the first surface, the first end being spaced apart from the first surface in a first direction perpendicular to the first surface, the first end of the buried layer has a first width in a second direction parallel to the first surface of the semiconductor substrate, the buried insulating layer has a second width in the second direction, and the second width is greater than the first width.
