

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12415312

Kind Code

B2

Date of Patent

September 16, 2025

Inventor(s)

Asgeirsson; Sigurdur et al.

Additive manufacturing system, method and corresponding components for making elastomeric structures

Abstract

A system for additive manufacturing a medical device, the system comprising a first dispensing system, a second dispensing system, a deposition apparatus, and a deposition substrate on a surface of which the deposition apparatus is configured to deposit at least one elastomeric material into a filament. The deposition apparatus receives the at least one elastomeric material from the first and second dispensing systems in proportions effecting a desired property in the medical device. The deposition apparatus may comprise heating and/or cooling elements, a sonic vibration module, and/or a pneumatic suck-back valve. The deposition substrate may have a configuration corresponding to a desired shape of the medical device and is configured to rotate and/or translate relative to the deposition apparatus. The system comprises a controller configured to control the deposition.

Inventors: Asgeirsson; Sigurdur (Foothill Ranch, CA), Dlab; Jiri (Foothill Ranch, CA), Sigfusson; Larus (Foothill Ranch, CA)

Applicant: Ossur Iceland ehf (Reykjavik, IS)

Family ID: 1000008821170

Assignee: OSSUR ICELAND EHF (Reykjavik, IS)

Appl. No.: 17/707070

Filed: March 29, 2022

Prior Publication Data

Document Identifier

Publication Date

US 20220219391 A1

Jul. 14, 2022

Related U.S. Application Data

Publication Classification

Int. Cl.: **B29C64/20** (20170101); **B29C64/106** (20170101); **B29C64/209** (20170101);
B29C64/227 (20170101); **B29C64/245** (20170101); **B29C64/295** (20170101);
B29C64/307 (20170101); **B29C64/343** (20170101); **B29K21/00** (20060101); **B33Y30/00**
(20150101); **B33Y40/00** (20200101)

U.S. Cl.:

CPC **B29C64/20** (20170801); **B29C64/209** (20170801); **B29C64/227** (20170801);
B29C64/245 (20170801); **B29C64/295** (20170801); **B29C64/343** (20170801);
B29C64/106 (20170801); B29C64/307 (20170801); B29K2021/00 (20130101);
B33Y30/00 (20141201); B33Y40/00 (20141201)

Field of Classification Search

CPC: B29C (64/20); B29C (64/106); B29C (64/118); B29C (64/112); B29C (64/209); B29C
(64/227); B29C (64/245); B29C (64/295); B29C (64/343); B33Y (30/00); B33Y (40/00)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
529719	12/1893	Eils	N/A	N/A
541275	12/1894	Hepp	N/A	N/A
2104742	12/1937	Fleischer	N/A	N/A
2414716	12/1946	Carson	N/A	N/A
2490586	12/1948	Embree	N/A	N/A
2680501	12/1953	Cunningham	N/A	N/A
2765159	12/1955	Garofalo	N/A	N/A
3019552	12/1961	Schleich	N/A	N/A
3081514	12/1962	Griswold	N/A	N/A
3125195	12/1963	Moore	N/A	N/A
3389451	12/1967	Specia et al.	N/A	N/A
3391048	12/1967	Dyer et al.	N/A	N/A
3468748	12/1968	Bassett	N/A	N/A
3661670	12/1971	Pierpont, Jr.	N/A	N/A
4107870	12/1977	Ausnit	N/A	N/A
4205152	12/1979	Mizuguchi et al.	N/A	N/A
4290170	12/1980	Brookstein et al.	N/A	N/A
4323756	12/1981	Brown et al.	N/A	N/A
4575330	12/1985	Hull	N/A	N/A
4674580	12/1986	Schuh et al.	N/A	N/A
4735418	12/1987	Engel	N/A	N/A

4777859	12/1987	Plummer, Jr.	N/A	N/A
4867834	12/1988	Alenskis et al.	N/A	N/A
4976091	12/1989	Salemka	53/503	G05D 9/12
4978564	12/1989	Douglas	N/A	N/A
5045147	12/1990	Benson et al.	N/A	N/A
5156629	12/1991	Shane et al.	N/A	N/A
5281181	12/1993	McCollum	N/A	N/A
5288287	12/1993	Castillo et al.	N/A	N/A
5372283	12/1993	Schmitkons et al.	N/A	N/A
5387245	12/1994	Fay et al.	N/A	N/A
5571208	12/1995	Caspers	N/A	N/A
5594652	12/1996	Penn et al.	N/A	N/A
5603122	12/1996	Kania	N/A	N/A
5702489	12/1996	Slemker	N/A	N/A
5713837	12/1997	Grim et al.	N/A	N/A
5781652	12/1997	Pratt	N/A	N/A
5853313	12/1997	Zheng	N/A	N/A
5888216	12/1998	Haberman	N/A	N/A
5901060	12/1998	Schall et al.	N/A	N/A
5928803	12/1998	Yasuda	N/A	N/A
6012494	12/1999	Balazs	N/A	N/A
6024712	12/1999	Iglesias et al.	N/A	N/A
6136039	12/1999	Kristinsson et al.	N/A	N/A
6165406	12/1999	Jang et al.	N/A	N/A
6176875	12/2000	Lenker et al.	N/A	N/A
6231616	12/2000	Helmy	N/A	N/A
6231617	12/2000	Fay	N/A	N/A
6264199	12/2000	Schaedel	N/A	N/A
6305769	12/2000	Thayer et al.	N/A	N/A
6358453	12/2001	Slemker et al.	N/A	N/A
6454972	12/2001	Morisette et al.	N/A	N/A
6463351	12/2001	Clynch	N/A	N/A
6508842	12/2002	Caspers	N/A	N/A
6554868	12/2002	Caspers	N/A	N/A
6592539	12/2002	Einarsson et al.	N/A	N/A
6626952	12/2002	Janusson et al.	N/A	N/A
6630093	12/2002	Jones	N/A	N/A
6645253	12/2002	Caspers	N/A	N/A
6926742	12/2004	Caspers et al.	N/A	N/A
6968246	12/2004	Watson et al.	N/A	N/A
6991444	12/2005	Laghi	N/A	N/A
7007370	12/2005	Gracias et al.	N/A	N/A
7118602	12/2005	Bjarnason	N/A	N/A
7160612	12/2006	Magill et al.	N/A	N/A
7162322	12/2006	Arbogast et al.	N/A	N/A
7169189	12/2006	Bjarnason et al.	N/A	N/A
7216678	12/2006	Baer	N/A	N/A
7225045	12/2006	Gothait et al.	N/A	N/A
7225050	12/2006	Sutula, Jr.	N/A	N/A
7300619	12/2006	Napadensky et al.	N/A	N/A

7351264	12/2007	Wilson	N/A	N/A
7438843	12/2007	Asgeirsson	N/A	N/A
7447558	12/2007	Pratt	N/A	N/A
7500846	12/2008	Eshed et al.	N/A	N/A
7575807	12/2008	Barvosa-Carter et al.	N/A	N/A
7708709	12/2009	Brewer	N/A	N/A
7785331	12/2009	Leisinger et al.	N/A	N/A
7851122	12/2009	Napadensky	N/A	N/A
7862624	12/2010	Tran	N/A	N/A
7867286	12/2010	Einarsson	N/A	N/A
8082696	12/2010	Oliver et al.	N/A	N/A
8142860	12/2011	Vanmaele et al.	N/A	N/A
8246888	12/2011	Hopkins et al.	N/A	N/A
8308817	12/2011	Egilsson et al.	N/A	N/A
8366789	12/2012	Summit	N/A	N/A
8424249	12/2012	Oliver	N/A	N/A
8475074	12/2012	Henry	N/A	N/A
8523951	12/2012	Kania	N/A	N/A
8652602	12/2013	Dolla	N/A	N/A
8668744	12/2013	McCarthy	N/A	N/A
8795386	12/2013	Pianykh et al.	N/A	N/A
8906113	12/2013	Mosler et al.	N/A	N/A
8940057	12/2014	Asgeirsson	N/A	N/A
8992183	12/2014	Perich et al.	N/A	N/A
9002496	12/2014	Elsey	N/A	N/A
9079337	12/2014	Lipton et al.	N/A	N/A
D744719	12/2014	Amarasiriwardena	N/A	N/A
9364348	12/2015	Sandahl	N/A	N/A
9398963	12/2015	King	N/A	N/A
9486333	12/2015	Wang et al.	N/A	N/A
9550327	12/2016	Swanson et al.	N/A	N/A
9669586	12/2016	Page	N/A	N/A
9757256	12/2016	Sandahl	N/A	N/A
9814607	12/2016	Zhe et al.	N/A	N/A
9901451	12/2017	Conway et al.	N/A	N/A
9970140	12/2017	Taninaka et al.	N/A	N/A
9993357	12/2017	Jonsson	N/A	N/A
9993973	12/2017	Barnhart	N/A	N/A
10005235	12/2017	Millar	N/A	N/A
10022917	12/2017	Pax	N/A	N/A
10028845	12/2017	Jonasson et al.	N/A	N/A
10064726	12/2017	Wei	N/A	N/A
10076880	12/2017	Page	N/A	N/A
10166726	12/2018	Fripp et al.	N/A	N/A
10286601	12/2018	Chang	N/A	N/A
10513089	12/2018	Tibbits et al.	N/A	N/A
10543643	12/2019	Sachs et al.	N/A	N/A
10549505	12/2019	Tibbits et al.	N/A	N/A
10633772	12/2019	Tibbits et al.	N/A	N/A

11312071	12/2021	Asgeirsson	N/A	B29C 64/106
2002/0043950	12/2001	Yim et al.	N/A	N/A
2002/0104973	12/2001	Kerekes	N/A	N/A
2002/0116847	12/2001	Yen	N/A	N/A
2002/0125790	12/2001	Horning et al.	N/A	N/A
2003/0090034	12/2002	Mülhaupt et al.	N/A	N/A
2003/0177749	12/2002	Jen	N/A	N/A
2003/0181990	12/2002	Phillips	N/A	N/A
2004/0030411	12/2003	Caspers	N/A	N/A
2004/0098136	12/2003	Caspers	N/A	N/A
2004/0137178	12/2003	Janusson et al.	N/A	N/A
2004/0143345	12/2003	Caspers	N/A	N/A
2004/0197519	12/2003	Elzey et al.	N/A	N/A
2004/0243251	12/2003	Carstens	N/A	N/A
2004/0244309	12/2003	Raue	N/A	N/A
2004/0260402	12/2003	Baldini et al.	N/A	N/A
2005/0101693	12/2004	Arbogast et al.	N/A	N/A
2005/0119777	12/2004	Arbogast et al.	N/A	N/A
2005/0149202	12/2004	Schaffer et al.	N/A	N/A
2005/0165338	12/2004	Iglesias et al.	N/A	N/A
2005/0227560	12/2004	Allred, III	N/A	N/A
2005/0265569	12/2004	Langberg et al.	N/A	N/A
2006/0016507	12/2005	Baer	N/A	N/A
2006/0020348	12/2005	Slemker et al.	N/A	N/A
2006/0159869	12/2005	Kramer et al.	N/A	N/A
2006/0184231	12/2005	Rucker	N/A	N/A
2006/0282175	12/2005	Haines et al.	N/A	N/A
2007/0036964	12/2006	Rosenberger et al.	N/A	N/A
2007/0055383	12/2006	King	N/A	N/A
2007/0073410	12/2006	Raugel	N/A	N/A
2007/0106173	12/2006	Korotko et al.	N/A	N/A
2007/0134486	12/2006	Bansal et al.	N/A	N/A
2007/0150069	12/2006	Takami et al.	N/A	N/A
2007/0162154	12/2006	Scott	N/A	N/A
2007/0163305	12/2006	Baer et al.	N/A	N/A
2007/0191965	12/2006	Colvin et al.	N/A	N/A
2007/0276510	12/2006	Becker et al.	N/A	N/A
2008/0027199	12/2007	Mazurek et al.	N/A	N/A
2008/0039757	12/2007	Nordt, III et al.	N/A	N/A
2008/0057809	12/2007	Rock	N/A	N/A
2008/0066393	12/2007	Sorenson	N/A	N/A
2008/0075850	12/2007	Rock	N/A	N/A
2008/0075930	12/2007	Kornbluh et al.	N/A	N/A
2008/0105324	12/2007	Baer	N/A	N/A
2008/0109103	12/2007	Gershenfeld et al.	N/A	N/A
2008/0188949	12/2007	Mackenzie	N/A	N/A
2008/0234458	12/2007	West	N/A	N/A
2008/0269420	12/2007	Tong et al.	N/A	N/A
2009/0176054	12/2008	Laib et al.	N/A	N/A

2009/0218307	12/2008	Davies et al.	N/A	N/A
2009/0233067	12/2008	Doornheim et al.	N/A	N/A
2009/0240344	12/2008	Colvin et al.	N/A	N/A
2009/0248168	12/2008	Tuke et al.	N/A	N/A
2010/0023149	12/2009	Sanders et al.	N/A	N/A
2010/0161076	12/2009	Pallari	N/A	N/A
2010/0168439	12/2009	Olson	N/A	N/A
2010/0191360	12/2009	Napadensky et al.	N/A	N/A
2011/0270414	12/2010	Laghi et al.	N/A	N/A
2011/0285052	12/2010	Wigand et al.	N/A	N/A
2012/0037263	12/2011	Malloy	N/A	N/A
2012/0068378	12/2011	Swanson et al.	N/A	N/A
2012/0091744	12/2011	McKnight et al.	N/A	N/A
2012/0094060	12/2011	Gershensfeld et al.	N/A	N/A
2012/0109336	12/2011	Laghi et al.	N/A	N/A
2012/0133080	12/2011	Moussa et al.	N/A	N/A
2012/0137611	12/2011	Oliver	N/A	N/A
2012/0241993	12/2011	Lipton et al.	N/A	N/A
2012/0308805	12/2011	Sella	N/A	N/A
2013/0001834	12/2012	El-Shiblani et al.	N/A	N/A
2013/0040091	12/2012	Dikovsky et al.	N/A	N/A
2013/0046394	12/2012	Lipschutz et al.	N/A	N/A
2013/0073068	12/2012	Napadensky	N/A	N/A
2013/0078415	12/2012	Rock	N/A	N/A
2013/0089642	12/2012	Lipson et al.	N/A	N/A
2013/0103125	12/2012	Radspieler et al.	N/A	N/A
2013/0150982	12/2012	Mosler et al.	N/A	N/A
2013/0246018	12/2012	Spadaccini et al.	N/A	N/A
2013/0249981	12/2012	Nakagawa et al.	N/A	N/A
2013/0282141	12/2012	Herr et al.	N/A	N/A
2014/0013962	12/2013	Lipton et al.	N/A	N/A
2014/0037873	12/2013	Cheung et al.	N/A	N/A
2014/0050811	12/2013	Lipton et al.	N/A	N/A
2014/0059734	12/2013	Toronjo	N/A	N/A
2014/0101816	12/2013	Toronjo	N/A	N/A
2014/0163445	12/2013	Pallari et al.	N/A	N/A
2014/0188260	12/2013	Layman et al.	N/A	N/A
2014/0276300	12/2013	Reinhardt et al.	N/A	N/A
2014/0277585	12/2013	Kelley et al.	N/A	N/A
2014/0311187	12/2013	Amarasiriwardena et al.	N/A	N/A
2015/0010461	12/2014	Cronin	N/A	N/A
2015/0014881	12/2014	Elsey	N/A	N/A
2015/0017411	12/2014	Wilkie et al.	N/A	N/A
2015/0032227	12/2014	Kettwig et al.	N/A	N/A
2015/0075033	12/2014	Cross et al.	N/A	N/A
2015/0142150	12/2014	Layman et al.	N/A	N/A
2015/0142159	12/2014	Chang	N/A	N/A
2015/0158244	12/2014	Tibbits et al.	N/A	N/A
2015/0174885	12/2014	Khan	N/A	N/A

2015/0250624	12/2014	Mosler et al.	N/A	N/A
2015/0297369	12/2014	Mosler et al.	N/A	N/A
2015/0321419	12/2014	Linthicum et al.	N/A	N/A
2015/0321420	12/2014	Karpas et al.	N/A	N/A
2015/0359644	12/2014	Sanders et al.	N/A	N/A
2015/0367375	12/2014	Page	N/A	N/A
2016/0000583	12/2015	Ballas et al.	N/A	N/A
2016/0009029	12/2015	Cohen et al.	N/A	N/A
2016/0058519	12/2015	Herr	N/A	N/A
2016/0096323	12/2015	Fry et al.	N/A	N/A
2016/0101594	12/2015	Tibbits et al.	N/A	N/A
2016/0167312	12/2015	Feinberg et al.	N/A	N/A
2016/0228255	12/2015	Samuelson et al.	N/A	N/A
2016/0263827	12/2015	Fripp et al.	N/A	N/A
2016/0297104	12/2015	Guillemette et al.	N/A	N/A
2016/0318247	12/2015	Schlachter	N/A	N/A
2016/0324666	12/2015	Barberio	N/A	N/A
2016/0332382	12/2015	Coward	N/A	B29C 64/277
2017/0021566	12/2016	Lund	N/A	N/A
2017/0027719	12/2016	Bache et al.	N/A	N/A
2017/0036402	12/2016	Zachariasen et al.	N/A	N/A
2017/0057167	12/2016	Van Tooren et al.	N/A	N/A
2017/0081573	12/2016	Kipke et al.	N/A	N/A
2017/0105853	12/2016	Jonsson et al.	N/A	N/A
2017/0106594	12/2016	Gardiner	N/A	N/A
2017/0120535	12/2016	MacCurdy et al.	N/A	N/A
2017/0173879	12/2016	Myerberg et al.	N/A	N/A
2017/0190121	12/2016	Aggarwal et al.	N/A	N/A
2017/0203509	12/2016	Stieghorst et al.	N/A	N/A
2017/0210064	12/2016	Aw et al.	N/A	N/A
2017/0216056	12/2016	Hill et al.	N/A	N/A
2017/0239888	12/2016	Ruiz et al.	N/A	N/A
2017/0252851	12/2016	Fulop	N/A	B22F 10/18
2017/0259502	12/2016	Chapiro et al.	N/A	N/A
2017/0312981	12/2016	Selbertinger	N/A	B29C 64/264
2017/0335268	12/2016	Maggiore	N/A	N/A
2018/0021140	12/2017	Angelini et al.	N/A	N/A
2018/0036952	12/2017	Hocker et al.	N/A	N/A
2018/0056602	12/2017	Susnjara et al.	N/A	N/A
2018/0098919	12/2017	Pallari et al.	N/A	N/A
2018/0112167	12/2017	Kang et al.	N/A	N/A
2018/0153716	12/2017	Martin	N/A	N/A
2018/0204379	12/2017	Mendoza et al.	N/A	N/A
2018/0207856	12/2017	Seriani	N/A	N/A
2018/0235779	12/2017	Dudding	N/A	N/A
2018/0236723	12/2017	Susnjara et al.	N/A	N/A
2018/0281295	12/2017	Tibbits et al.	N/A	N/A
2018/0281340	12/2017	Brienza et al.	N/A	N/A

2018/0296343	12/2017	Wei	N/A	B33Y 50/00
2018/0297280	12/2017	Silvestro	N/A	B29C 64/188
2018/0353308	12/2017	Tompkins	N/A	N/A
2018/0368996	12/2017	Van Vliet et al.	N/A	N/A
2018/0369451	12/2017	Rapoport et al.	N/A	N/A
2018/0370141	12/2017	Eller et al.	N/A	N/A
2019/0039309	12/2018	Busbee	N/A	A43B 1/00
2019/0039310	12/2018	Busbee et al.	N/A	N/A
2019/0053917	12/2018	Mosler	N/A	N/A
2019/0053919	12/2018	Egilsson et al.	N/A	N/A
2019/0070345	12/2018	McBride et al.	N/A	N/A
2019/0099952	12/2018	Macneish, III et al.	N/A	N/A
2019/0106593	12/2018	Kenney et al.	N/A	N/A
2019/0142406	12/2018	Amplatz et al.	N/A	N/A
2019/0183663	12/2018	Will et al.	N/A	N/A
2019/0270240	12/2018	Wolf	N/A	B29C 64/209
2019/0272346	12/2018	Weeger et al.	N/A	N/A
2019/0283319	12/2018	Rhoads	N/A	B05B 17/06
2019/0336749	12/2018	Daglow	N/A	B29C 64/106
2019/0344494	12/2018	Cropper et al.	N/A	N/A
2020/0016832	12/2019	Yuwaki	N/A	B29C 64/106
2020/0016833	12/2019	Yuwaki et al.	N/A	N/A
2020/0100920	12/2019	Finke	N/A	N/A
2020/0189187	12/2019	Streicher	N/A	B29C 64/20
2020/0247053	12/2019	Rodriguez et al.	N/A	N/A
2020/0289295	12/2019	Koppe	N/A	N/A
2020/0324464	12/2019	Reese et al.	N/A	N/A
2021/0030566	12/2020	Siewert et al.	N/A	N/A
2021/0068987	12/2020	Koppe et al.	N/A	N/A
2021/0129443	12/2020	Plott et al.	N/A	N/A
2021/0145613	12/2020	Anderson et al.	N/A	N/A
2021/0162651	12/2020	Schweizer et al.	N/A	N/A
2021/0197490	12/2020	Budge et al.	N/A	N/A
2021/0338457	12/2020	Albrecht-Laatsch et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
6615	12/2003	AT	N/A
2398059	12/2000	CA	N/A
3114854	12/2019	CA	N/A
103876263	12/2013	CN	N/A
105287064	12/2015	CN	N/A

106003728	12/2015	CN	N/A
107351375	12/2016	CN	N/A
106667629	12/2017	CN	N/A
109414330	12/2018	CN	N/A
110461277	12/2018	CN	N/A
112140529	12/2019	CN	N/A
917687	12/1953	DE	N/A
10018987	12/2000	DE	N/A
10153796	12/2002	DE	N/A
20309318	12/2002	DE	N/A
202008015143	12/2008	DE	N/A
202009000527	12/2008	DE	N/A
102011119591	12/2012	DE	N/A
102012009757	12/2012	DE	N/A
102013102471	12/2013	DE	N/A
102014011373	12/2015	DE	N/A
102014219570	12/2015	DE	N/A
102016201002	12/2016	DE	N/A
202016001130	12/2016	DE	N/A
102016108631	12/2016	DE	N/A
202017106997	12/2017	DE	N/A
102017106903	12/2017	DE	N/A
202019100501	12/2018	DE	N/A
102012017324	12/2018	DE	N/A
102017126465	12/2018	DE	N/A
102018106573	12/2018	DE	N/A
102018111442	12/2018	DE	N/A
102018124516	12/2019	DE	N/A
102018127117	12/2019	DE	N/A
102012022484	12/2019	DE	N/A
102018131550	12/2019	DE	N/A
102018133486	12/2019	DE	N/A
1274559	12/2002	EP	N/A
0876130	12/2005	EP	N/A
1854621	12/2006	EP	N/A
2090273	12/2008	EP	N/A
2568935	12/2012	EP	N/A
2599464	12/2012	EP	N/A
3100704	12/2015	EP	N/A
2599464	12/2016	EP	N/A
3156216	12/2016	EP	N/A
3243632	12/2016	EP	N/A
3300700	12/2017	EP	N/A
3454792	12/2018	EP	N/A
2459361	12/2018	EP	N/A
1243060	12/1959	FR	N/A
1331581	12/1962	FR	N/A
2095097	12/1971	FR	N/A
2479923	12/1980	FR	N/A
2583334	12/1985	FR	N/A

2956590	12/2010	FR	N/A
2455167	12/2008	GB	N/A
H0742024	12/1994	JP	N/A
2003533367	12/2002	JP	N/A
2017035811	12/2016	JP	N/A
0069747	12/1999	WO	N/A
0178968	12/2000	WO	N/A
03016067	12/2002	WO	N/A
03051241	12/2002	WO	N/A
2006113585	12/2005	WO	N/A
2006135851	12/2005	WO	N/A
2013072064	12/2012	WO	N/A
2013121230	12/2012	WO	N/A
2013142343	12/2012	WO	N/A
2014025089	12/2013	WO	N/A
2014130878	12/2013	WO	N/A
2014144985	12/2013	WO	N/A
2015017421	12/2014	WO	N/A
2015059502	12/2014	WO	N/A
2015084422	12/2014	WO	N/A
2015139095	12/2014	WO	N/A
2015197495	12/2014	WO	N/A
2016033469	12/2015	WO	N/A
2016057853	12/2015	WO	N/A
2017011753	12/2016	WO	N/A
2017012888	12/2016	WO	N/A
2017019681	12/2016	WO	N/A
2017062690	12/2016	WO	N/A
2017079475	12/2016	WO	N/A
2017081040	12/2016	WO	N/A
2017136405	12/2016	WO	N/A
2017152142	12/2016	WO	N/A
2017194479	12/2016	WO	N/A
2018044759	12/2017	WO	N/A
2018054966	12/2017	WO	N/A
2018088965	12/2017	WO	N/A
2018151923	12/2017	WO	N/A
2018183803	12/2017	WO	N/A
2018187514	12/2017	WO	N/A
2019091716	12/2018	WO	N/A
2019110170	12/2018	WO	N/A
2019179894	12/2018	WO	N/A
2019219514	12/2018	WO	N/A
2020069817	12/2019	WO	N/A
2020074374	12/2019	WO	N/A
2020120187	12/2019	WO	N/A
2020126501	12/2019	WO	N/A
2021101806	12/2020	WO	N/A

OTHER PUBLICATIONS

Klute et al., "Prosthetic Liners for Lower Limb Amputees: A Review of the Literature," *Prosthetics and Orthotics International*, vol. 34, No. 2, Jun. 2010, pp. 146-153. cited by applicant

Franzino, "3 Ways to Adhere Silicone to Silicone," *Albright Technologies Monthly Insider*, Issue 17, Mar. 2013, 2 Pages. cited by applicant

"CF19-2186; Medium Cure Rate, General Purpose Silicone Elastomer," NuSil, May 21, 2014, retrieved from https://nusil.com/en/product/CF19-2186_medium-cure-rate-general-purpose-silicone-elastomer?h=cf19 on Jan. 3, 2020. cited by applicant

"MED-4950; Liquid Silicone Rubber," NuSil, May 16, 2014, retrieved from https://nusil.com/en/product/MED-4950_liquid-silicone-rubber?h=med-4950 on Jan. 3, 2020, 3 Pages. cited by applicant

Ventola, "Medical Applications for 3D Printing: Current and Projected Uses," *P&T*, vol. 39, No. 10, Oct. 2014, pp. 704-712. cited by applicant

Femmer et al., "Print Your Own Membrane: Direct Rapid Prototyping of Polydimethylsiloxane," *Royal Society of Chemistry*, vol. 14, 2014, pp. 2610-2613. cited by applicant

"A True Rotary 3D Printer?" *element14*, Jun. 27, 2015, retrieved from www.element14.com/community/thread/25031a-true-rotary-3, Oct. 22, 2018. cited by applicant

Ostermeier, "3D Printing With Silicone," *Assembly Magazine*, Oct. 2, 2015, pp. 1-4. cited by applicant

Coulter et al., "4D Printing Inflatable Silicone Structures," *3D Printing and Additive Manufacturing*, vol. 2, No. 3, 2015, pp. 1-6. cited by applicant

Cagle, "A Computational Tool to Enhance Clinical Selection of Prosthetic Liners for People with Lower Limb Amputation," *University of Washington*, 2016, pp. 1-154. cited by applicant

Hoy, "Design and Implementation of a Three-Dimensional Printer Using a Cylindrical Printing Process," *Electrical Engineering Department, California Polytechnic State University*, 2016, pp. 1-31. cited by applicant

Momeni et al., "A Review of 4D Printing," *Materials and Design*, vol. 122, Mar. 1, 2017, pp. 42-79. cited by applicant

O'Bryan et al., "Self-Assembled Micro-Organogels for 3D Printing Silicone Structures," *Science Advances*, vol. 3, May 10, 2017, pp. 1-8. cited by applicant

Rios, "Evaluation of Advanced Polymers for Additive Manufacturing," *Oak Ridge National Laboratory*, Sep. 8, 2017, pp. 1-22. cited by applicant

"Rethinking Foam-Carbon's Lattice Innovation," retrieved from www.carbon3d.com, Dec. 6, 2017, pp. 1-9. cited by applicant

Kiessling et al., "Gravity-Drawn Silicone Filaments: Production, Characterization, and Wormlike Chain Dynamics," *American Chemical Society, Applied Materials & Interfaces*, vol. 9, 2017, pp. 39916-39920. cited by applicant

Low et al., "Perspective on 3D Printing of Separation Membranes and Comparison to Related Unconventional Fabrication Techniques," *Journal of Membrane Science*, 2017, pp. 596-613. cited by applicant

Tian et al., "Silicone Foam Additive Manufacturing by Liquid Rope Coiling," *Science Direct*, 2017, pp. 196-201. cited by applicant

Dhokia et al., "The Design and Manufacture of a Prototype Personalized Liner for Lower Limb Amputees," *Science Direct*, 2017, pp. 476-481. cited by applicant

Jasiuk et al., "An Overview on Additive Manufacturing of Polymers," *The Minerals, Metal & Materials Society*, vol. 70, No. 3, Jan. 25, 2018, pp. 275-283. cited by applicant

Woodford, "Centrifuges," Jun. 24, 2018, retrieved from www.explainthatstuff.com/centrifuges on Nov. 7, 2018, pp. 1-10. cited by applicant

"How Liners Work," *Ottobock*, retrieved from www.ottobockus.com/prosthetics on Oct. 22, 2018, 1 Page. cited by applicant

“Technology: The Process in a Nutshell,” Spectroplast AG, retrieved from www.spectroplast.com/technology on Oct. 31, 2018, pp. 1-5. cited by applicant

Liravi et al., “A Hybrid Additive Manufacturing Method for the Fabrication of Silicone Bio-Structures: 3D Printing Optimization and Surface Characterization,” Elsevier: Materials and Design, 2018, pp. 46-61. cited by applicant

Ruiz et al., “3D Printing Assisted Method of Manufacturing a Perforated Silicone Prosthetic Limb Liner,” RESNA Annual Conference, 2017, pp. 1-4. cited by applicant

Zhakeyev et al., “Additive Manufacturing: Unlocking the Evolution of Energy Materials,” Advanced Science, vol. 4 2017, pp. 1-44. cited by applicant

Javaid et al., “Current Status and Challenges of Additive Manufacturing in Orthopaedics: An Overview,” Journal of Clinical Orthopaedics and Trauma, 2019. pp. 380-386. cited by applicant

McColl et al., “Design and Fabrication of Melt Electrowritten Tubes Using Intuitive Software,” Materials and Design, 2018, pp. 46-58. cited by applicant

“3D Printing of Silicone Parts in Additive Manufacturing,” Capri Systec Ltd, May 22, 2018, pp. 1-3. cited by applicant

Li et al., “Review of 3D Printable Hydrogels and Constructs,” Materials and Design, Issue 159, 2018, pp. 20-38. cited by applicant

Helmenstine, “What Is Centripetal Force? Definition and Equations,” Thought Co., Sep. 21, 2018, pp. 1-3. cited by applicant

Liravi et al., “Additive Manufacturing of Silicone Structures: A Review and Prospective,” Additive Manufacturing, Issue 24, 2018, pp. 232-242. cited by applicant

“3D Printing With Silicones—A Breakthrough in Additive Manufacturing,” retrieved from www.plastics.gl/3d-printing-2/3d-printing-with-silicones-a-breakthrough-in-additive-manufacturing/ on Oct. 31, 2018. cited by applicant

Culmone et al., “Additive Manufacturing of Medical Instruments: A State-of-the-Art Review,” Additive Manufacturing, Issue 27, 2019, pp. 461-473. cited by applicant

Ooi, “How to 3D Print Rubber-Like Materials,” All3DP, retrieved from <https://all3dp.com/2/how-to-3d-print-rubber-like-materials/> on Aug. 13, 2019, pp. 1-7. cited by applicant

“Progressive Cavity Pumps—Volumetric Dosing Systems,” retrieved from www.viscotec.de/en/technology/ retrieved on Aug. 13, 2019. cited by applicant

Yuan et al., “Polymeric Composites for Powder-Based Additive Manufacturing: Materials and Applications,” Progress in Polymer Science, vol. 91, 2019, pp. 141-168. cited by applicant

Chen et al., “3D Printed Multifunctional, Hyperelastic Silicone Rubber Foam,” Advanced Functional Materials, vol. 29, Issue 1900469, 2019, pp. 1-9. cited by applicant

“About the Silicone Molding Design Manual,” Albright Technologies 6th Edition, pp. 1-248. cited by applicant

Porter et al., “Additive Manufacturing Utilizing Stock Ultraviolet Curable Silicone,” Solid Freeform Fabrication 2017: Proceedings of the 28th Annual International Solid Freeform Fabrication Symposium, pp. 1-13. cited by applicant

Liravi et al., “A Hybrid Method for Additive Manufacturing of Silicone Structures,” Solid Freeform Fabrication 2017: Proceedings of the 28th Annual International Solid Freeform Fabrication Symposium, pp. 1-21. cited by applicant

Toursangsaraki, “A Review of Multi-Material and Composite Parts Production by Modified Additive Manufacturing Methods”, Jun. 12, 2018, pp. 1-25. cited by applicant

Unkovskiy et al., “Direct 3D Printing of Silicone Facial Prostheses: A Preliminary Experience in Digital Workflow,” The Journal of Prosthetic Dentistry, Aug. 2018, pp. 1-6. cited by applicant

Coulter et al., “Production Techniques for 3D Printed Inflatable Elastomer Structures. Part 1—Fabricating Air-Permeable Forms and Coating with Inflatable Silicone Membranes via Spray Disposition”, Mar. 2018, pp. 1-17. cited by applicant

Duoss et al., “Three-Dimensional Printing of Elastomeric, Cellular Architectures with Negative

Stiffness,” Advanced Functional Materials, vol. 24, 2014, pp. 4905-4913. cited by applicant

“MED-4901; Liquid Silicone Rubber,” NuSil, Nov. 2018, retrieved from https://nusil.com/product/med-4901_liquid-silicone-rubber on Nov. 11, 2019, 3 Pages. cited by applicant

“MED-6345; Soft Silicone Adhesive,” NuSil, Nov. 2018, retrieved from https://nusil.com/en/product/MED-6345_soft-silicone-adhesive?h=MED-6345 on Nov. 11, 2019, 3 Pages. cited by applicant

Office Action from corresponding European Patent Application No. 19836172.7-1103, Aug. 5, 2022. cited by applicant

International Search Report from PCT Application No. PCT/US2019/060863, Apr. 15, 2020. cited by applicant

International Search Report from PCT Application No. PCT/US2019/060881, Apr. 20, 2020. cited by applicant

Hsu, L.H.: “The development of a rapid prototyping prosthetic socket coated with a resin layer for transtibial amputees”, Prosthetics and Orthotics International, vol. 34, No. 1, Mar. 1, 2010 (Mar. 1, 2010), pp. 37-45. cited by applicant

Nicholas Herbert et al, “A preliminary investigation into the development of 3-D printing of prosthetic sockets”, Journal of Rehabilitation Research and Development, vol. 42, No. 2, Jan. 1, 2005 (Jan. 1, 2005), US, pp. 141. cited by applicant

Primary Examiner: Moreno Hernandez; Jerzi H

Attorney, Agent or Firm: Workman Nydegger

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. application Ser. No. 16/681,096, filed Nov. 12, 2019, incorporated herein. This application incorporates by reference U.S. application Ser. No. 16/680,959 entitled “MEDICAL DEVICE INCLUDING A STRUCTURE BASED ON FILAMENTS,” by the certain inventors of this disclosure and filed on Nov. 12, 2019. This application also incorporates by reference U.S. provisional application No. 62/759,237, filed on Nov. 12, 2018, and 62/760,030, filed on Nov. 12, 2018.

FIELD OF THE DISCLOSURE

(1) The disclosure relates to the field of additive manufacturing, and more particularly to an additive manufacturing system, method, and corresponding components for making structures based on filaments and elastomeric materials.

BACKGROUND

(2) Additive manufacturing is an increasingly important manufacturing method, comprising numerous applications across many industries. Additive manufacturing, also known as “3D printing,” is regarded as a transformative method for industrial production which facilitates the production of a three-dimensional article from a material according to a computer-aided design (CAD) of a definitive article by computer-aided manufacturing (CAM). In this sense, additive manufacturing is a digital revolution of analog manufacturing processes. Efforts have been made to apply additive manufacturing to articles formed from numerous types of materials, including polymeric materials, a subset of which are elastomeric materials.

(3) Additive manufacturing of elastomeric materials, including silicone, are limited by several factors. In many existing systems, the fluidity of the elastomeric material requires the provision of

a vat of liquid elastomeric material or precursor, in which a nozzle deposits curing agents to form a solid article from the liquid elastomeric material in situ, with leftover elastomeric material drained and washed away after the formation process is completed. Other additive manufacturing systems require a low- or room-temperature curing or vulcanizing elastomeric material so that the mass of elastomeric material quickly cures and does not deform during the formation process, as adding multiple layers of elastomeric material may not be accurately performed if the elastomeric material is uncured. Yet other additive manufacturing systems require that individual, discrete beads or droplets of elastomeric material are added one at a time to build a solid three-dimensional elastomeric structure from the base up.

(4) Existing systems for elastomeric additive manufacturing, including those that utilize silicone, compromise the structural quality of the final product by using low viscosity, low-temperature-curing materials to enable the deposition process. It is not known in the art how to provide a smooth, consistent texture of deposited material having desired material properties. In medical applications, existing additive manufacturing systems preclude the additive manufacturing of medical-grade silicone, having the requisite strength, biocompatibility, and elasticity of conventionally manufactured medical products. Existing additive manufacturing systems have therefore been unable to meet the demand for articles made from medical-grade silicone that can exhibit the mechanical and chemical properties obtained from existing articles including medical devices formed by other, conventional manufacturing methods such as molding and extrusion.

(5) In healthcare applications, silicone is a desirable elastomeric material due to its biocompatibility and long history of implanted medical devices. Due to confirmatory biological testing, use of existing medical-grade silicone materials is desirable to reduce the time from concept to market. Despite its accepted use in healthcare applications, silicone materials are thick and viscous and require high pressure to be injected into molds to manufacture a precise article, such as through injection molding and transfer molding processes. Challenges are imposed in additive manufacturing because it is difficult to precisely extrude significantly viscous silicone onto a substrate into a definitive shape with high pressure if no mold is employed, while accounting for curing and shrinkage rates, as the silicone often deforms, sags, or otherwise loses its desired shape before curing.

(6) While silicone materials can be processed and formed in small batches in a design phase, difficulties arise when scaling up production of silicone as not only is its viscosity difficult to manage, but other factors must be considered including curing temperature and time, entrapment of air or bubbles, shrinkage, mixture of parts, and cross-linking to manufacture medically-accepted articles. Silicone is a thermoset polymeric material and will cure into its given shape of a strong, dimensionally stable and heat- and chemical-resistant article, but such advantages also require that the structure into which the silicone cures must be made correctly at the onset as later adaptation is typically not feasible. This limits the customizability of elastomeric structures formed through additive manufacturing. Any additive manufacturing process on a commercially scalable level should be able to preserve the mechanical properties of a cured silicone, such as toughness and elasticity and other properties desirable in a medical-grade silicone article while offering high throughput and precision.

(7) Existing systems for additive manufacturing may provide for only a monolithic or single-property structure, as only a single grade or blend of material can be deposited. The structures and functions of additive-manufactured articles are limited to what can be achieved through a single material property. There is a need for an additive manufacturing system that can accurately deposit material having different properties to attain a final product with desired properties in desired regions.

(8) Another problem of existing manufacturing systems is that many are limited to depositing a single discrete bead of elastomeric material at a time, limiting the construction of 3D-printed articles to discontinuous structures that are a sum of individual drops or beads, rather than

comprising smooth and continuous layers, filaments, or structures with varying properties.

(9) Many production and manufacturing methods are limited to providing a mold in which elastomeric material may be injected and thereafter cured to attain a desired shape and properties. This considerably limits the design and manufacturing flexibility when preparing an article. Because existing methods are limited to processes that deposit discrete beads or inject elastomeric material into negative molds, there is a need for a system that can deposit filaments of elastomeric material to form a structure with desired properties at desired locations.

(10) Existing systems are directed to implementations where an article is built from the bottom up and only in cartesian coordinates. In other systems, the effects of gravity on uncured or partially cured polymer materials limit the dimensions of the article, as too much material added to the article causes distortions from gravity, particularly combined with the effects of viscosity and curing rates as discussed above. There is a need for an additive manufacturing system that overcomes the effects of gravity and allows for additive manufacturing of articles in multiple dimensions.

(11) Solutions that attempt to perform additive manufacturing on a rotating build surface or substrate do not provide for the additive manufacturing of medical-grade silicones, which require particular viscosities and cure rates, but rather as limited to systems that utilize shavers or cutters that remove extra, unwanted deposited material. These systems also are configured to allow material to drip or fall away from the substrate. There is no teaching of using a rotating substrate that achieves desired printing of medical-grade structures from silicone without cutters and dripping configurations to conductive negative manufacturing procedures.

(12) There is a need for an additive manufacturing system that overcomes the limitations of existing systems, namely that low-quality elastomeric materials are used to enable deposition limited to depositing discrete beads, that properties of materials are monolithic and cannot be dynamic to account for different structural and functional needs at different parts or components of an elastomeric additive-manufactured article, and that the methods for additive manufacturing are limited to bottom-up approaches, with gravity effects unmitigated and unaddressed. It is highly desirable to use known silicone materials having confirmatory biological testing in additive manufacturing to create precise silicone-based structures suitable for medical devices.

SUMMARY

(13) The additive manufacturing system, method and corresponding components for making silicone structures of the disclosure advantageously provides a system for providing material in desired quantities and at desired locations of an article with an improved dispensing and deposition apparatus, resulting in smooth, continuous depositions of beads, filaments, or layers of material with controlled variation of desired properties and at desired locations. The additive manufacturing system of the disclosure may comprise three primary dispensing systems, including a first dispensing system, a secondary dispensing system, and a deposition apparatus. The additive manufacturing system may further comprise a deposition substrate arranged to cooperate with the three primary dispensing systems.

(14) The first dispensing system may comprise a vat or reservoir of at least one additive manufacturing material, the material arranged to be drawn from the vat or reservoir, and transmitted to the secondary dispensing system as the additive manufacturing system forms an article from the material. A separate vat or reservoir may correspond to different materials. Silicone is often of a two-part, 1:1 mix ratio material preferably drawn from at least two reservoirs, although more reservoirs may create different combinations of silicone compositions with desired properties at desired locations of an additively manufactured article.

(15) A secondary dispensing system may comprise a proportioning column or device and control valves arranged to correspond to or cooperate with the respective vat or reservoir of the first dispensing system. The proportioning column preferably draws the material from the reservoir and stores it in a volume of the proportioning column. The control valves associated with the

proportioning column are arranged to control a rate and volume according to which the material is stored in the proportioning column and at which it may be transmitted towards the deposition apparatus. A plurality of proportioning columns and corresponding control valves may be provided and may each correspond to a respective vat or reservoir in the first dispensing system, with each of the proportioning columns, control valves, and vats containing different materials or blends of materials selected and proportioned to impart desired properties to the final article.

(16) The deposition apparatus is arranged to receive the material from the proportioning column in rates and volumes that correspond to properties desired at specific locations along with an article being formed. The deposition apparatus comprises a dynamic mixer to blend the material, which as discussed may comprise two or more components or separate parts blended before being deposited.

(17) The deposition apparatus may have a modular construction and comprise heat transfer components, sonic vibration components, pneumatic stop valves, and other modules as may enable a smooth, consistent deposition of the material while varying desired properties. A nozzle may be provided for depositing the material onto the article.

(18) A deposition substrate may be arranged to cooperate with the additive manufacturing system. The deposition substrate may comprise a moving substrate on which the material may be deposited and cured. The moving substrate may counteract or overcome the effects of gravity on the deposited material, thereby keeping it in a desired dimensional state as it cures. The deposition substrate allows for forming an article with desired features and properties in desired locations in different paths or orders than are available in existing additive manufacturing systems, particularly for materials like medical-grade silicone. The deposition substrate may comprise heat transfer components for tailoring the cure rate of the deposited material and improving the process of deposition as the material may better retain a desired shape and configuration.

(19) These and other features of the present disclosure will become better understood regarding the following description, appended claims, and accompanying drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a perspective view of an additive manufacturing system according to an embodiment.

(2) FIG. 2 is a perspective view of a secondary dispensing system of the additive manufacturing system of FIG. 1.

(3) FIG. 3 is an elevational view of a deposition apparatus of the additive manufacturing system of FIG. 1.

(4) FIG. 4 is a cutaway elevational view of a material flow portion of the additive manufacturing system of FIG. 1.

(5) FIG. 5A is a perspective view of a deposition apparatus of the additive manufacturing system of FIG. 1.

(6) FIG. 5B is an elevational cross-sectional view of the deposition apparatus of FIG. 5A taken along the line VB-VB.

(7) FIG. 6 is a perspective cutaway view of the deposition apparatus of FIG. 5A.

(8) FIG. 7A is a cutaway detail view VIIA of the pneumatic valve assembly of the deposition apparatus of FIG. 5A.

(9) FIG. 7B is a cutaway elevational view of a heat transfer system in an embodiment of a deposition apparatus of an additive manufacturing system according to the disclosure.

(10) FIG. 8 is a cutaway perspective view of a coextrusion deposition apparatus comprising parallel dynamic mixing apparatuses according to an embodiment of an additive manufacturing system according to the disclosure.

(11) FIG. 9 is an elevational view of a deposition apparatus and a deposition substrate according to

an embodiment of an additive manufacturing system according to the disclosure.

(12) FIG. **10** is a plan view of the deposition apparatus and deposition substrate of FIG. **9**.

(13) FIG. **11** is an elevational cutaway view of a deposition apparatus according to an embodiment of an additive manufacturing system according to the disclosure.

(14) FIG. **12A** is a plan view of a deposition substrate according to the additive manufacturing system of FIG. **9**.

(15) FIG. **12B** is a cutaway elevational view of the deposition substrate of FIG. **12A**.

(16) FIG. **12C** is an elevational view of the deposition substrate of FIG. **12A** according to an embodiment.

(17) FIG. **13A** is a perspective view of a nozzle of a deposition apparatus according to an embodiment.

(18) FIG. **13B** is a perspective view of the nozzle of FIG. **13A** and a deposition substrate according to an embodiment.

(19) FIGS. **14A** and **14B** are perspective views of a mounting mechanism according to an embodiment of the disclosure.

(20) FIG. **14C** is a perspective view of a mounting mechanism and a deposition substrate according to an embodiment of the disclosure.

(21) The drawing figures are not necessarily drawn to scale, but instead are drawn to provide a better understanding of the components, and are not intended to be limiting in scope, but to provide exemplary illustrations. The figures illustrate exemplary configurations of an additive manufacturing system, and in no way limit the structures or configurations of the additive manufacturing system, methods, and corresponding components according to the present disclosure.

DETAILED DESCRIPTION OF VARIOUS EMBODIMENTS

(22) The additive manufacturing system, method, and corresponding components for making elastomeric structures of the disclosure address the limitations of existing additive manufacturing systems by providing a first dispensing system, a secondary dispensing system, and a deposition apparatus according to embodiments of the disclosure. The additive manufacturing system achieves controlled variability of material properties throughout a produced article, with a dynamic mixing apparatus that creates smooth, consistent material blends for precise, discrete and/or continuous deposits of material such as filaments of elastomeric material that chemically bond together to define an elastomeric 3D-printed article. A dynamic deposition substrate may be arranged for cooperating with the deposition apparatus to overcome the effects of gravity and to facilitate dynamic orders or paths of additive manufacturing. Combinations of these components may be provided with other known components, and do not have to be used in combination with one another.

(23) Structures that can be manufactured according to the system, methods, and components thereof are described in U.S. application Ser. No. 16/680,959 entitled “MEDICAL DEVICE INCLUDING A STRUCTURE BASED ON FILAMENTS,” by certain inventors of this disclosure, and concurrently filed on Nov. 12, 2019.

(24) The Applicant incorporates herein by reference the “6.sup.th Edition Silicone Design Manual by Albright Technologies Inc.,” at www.Albright1.com, and retrieved on Nov. 8, 2018, published by Albright Technologies of Leominster, MA, U.S.A.

(25) FIG. **1** depicts in perspective view an additive manufacturing system **100** according to an embodiment of the disclosure. A first dispensing system **102** comprises vats or reservoirs containing at least one material and is connected to a secondary dispensing system **104**, which provides material from the first dispensing system **102** to a deposition apparatus **106** in desired proportions. The additive manufacturing system **100** may be arranged to cooperate with a deposition substrate **130**, as will be described further herein.

(26) Examples of medical-grade elastomer that may be utilized by the additive manufacturing

system **100** include silicone, polyurethane, or other elastomeric materials. For the disclosure, the embodiments will be described as formed from medical-grade silicone. An example of a medical-grade silicone is obtainable from NuSil Technology of Carpinteria, Calif., under product designations MED-4901, MED-6340, or MED-6345, although other silicone compositions can be used.

(27) FIG. 2 is a perspective view of a secondary dispensing system **104**, as shown in the embodiment of FIG. 1. The secondary dispensing system **104** comprises a plurality of proportioning columns or devices **112A**, **112B**, **112C**, **112D**. Each of the proportioning columns **112A**, **112B**, **112C**, **112D** is connected to a corresponding vat or reservoir in the first dispensing system **102** via a respective reservoir feed line **108A**, **108B**, **108C**, **108D**. Elastomeric material, additives, pigments, crosslinking agents, curing agents, or any other suitable component may be provided from the reservoirs in the first dispensing system **102** to the secondary dispensing system **104** via the reservoir feed lines **108A**, **108B**, **108C**, **108D**. In embodiments, the elastomeric material may be liquid silicone material comprising two parts, which may be cured to form a solid silicone structure.

(28) The proportioning columns **112A**, **112B**, **112C**, **112D** may be configured to receive within an interior volume thereof (not shown) a quantity of material or other material from the vats or reservoirs in the first dispensing system **102**, and to distribute the material via respective proportioning control valves **114A**, **114B**, **114C**, **114D** toward the deposition apparatus **106**. The proportioning columns **112A**, **112B**, **112C**, **112D** may draw the material from the vats in the first dispensing system **102** in a controlled manner via receiving control valves **110A**, **110B**, **110C**, **110D**. The receiving control valves **110A**, **110B**, **110C**, **110D** are arranged to maintain a specified volume of material in the proportioning columns **112A**, **112B**, **112C**, **112D** and/or to provide a required amount of material based on the deposition process downstream of the proportioning columns **112A**, **112B**, **112C**, **112D**.

(29) The receiving control valves **110A**, **110B**, **110C**, **110D** may be servo-controlled or otherwise controlled, and are arranged to communicate with a controller. The controller may comprise a mathematical model and/or a process control scheme to direct the receiving control valves **110A-D** and the proportioning control valves **114A**, **114B**, **114C**, **114D** to open and transmit the material in the interior volume of the proportioning columns or devices **112A**, **112B**, **112C**, **112D** to the deposition apparatus **106** in desired proportions to effect desired properties at desired locations in the article.

(30) By providing the controller in communication with the proportioning control valves **114A**, **114B**, **114C**, **114D**, desired amounts of material types, including the two parts of a liquid silicone material, or other additives, may be provided at specific times corresponding to a moment during a deposition process at which the deposition apparatus **106** will deposit the material or additives at a desired location on the formed article. As the proportioning columns **112A**, **112B**, **112C**, **112D**, and respective proportioning control valves **114A**, **114B**, **114C**, **114D** act simultaneously and cooperatively, infinitely many combinations of the two parts of the liquid silicone material and other additives may be defined, providing the formed article with precise combinations of material to form continuous sections, features, and components having desired properties and without interruption to the flow of the material through system **100**, as opposed to the monolithic articles formed by existing methods of additive manufacturing or by methods such as injection molding, which have unvarying properties throughout the articles.

(31) For example, the secondary dispensing system **104** may be arranged to create material blends comprising elastomeric polymeric materials, such as parts A and B of a two-part silicone material mix, and additives that may influence the cure times of the material blend, the cure temperature of the material blend, color, stiffness, strength, elasticity, or any other property of particular regions of the final article. The secondary dispensing system **104** advantageously may provide elastomeric materials and additives in any proportions needed, so infinitely many combinations of properties

may be attained and at desired locations along with the article.

(32) While in the embodiment of FIG. 2, only four proportioning columns **112A**, **112B**, **112C**, **112D** are depicted, it will be appreciated that fewer or more proportioning columns may be utilized as deemed suitable. For example, in large or complex articles, more proportioning columns may be provided to supply additional specialized additives or different types of polymeric materials. For example, silicone oils may be provided for adjusting a durometer of certain materials, accelerators may be provided to adjust cure times, and other agents or additives may be provided for fine-tuning the properties of the final materials in the article. Redundant vats or proportioning columns may be provided to facilitate continuous deposition of the article when a particular vat or proportioning column runs out of a material part.

(33) FIG. 3 is an elevational view of a deposition apparatus **106** according to the embodiment of the additive manufacturing system **100** introduced in FIG. 1. The deposition apparatus **106** may comprise a deposition head **120** and a feed component **122**, the deposition head **120** controlling the deposition of material onto an article, and the feed component **122** controlling a rate and quantity at which material is fed from the secondary dispensing system **104** to the deposition head **120**. The feed component **122** may comprise a material inlet **123** configured to receive material at or from the proportioning control valves **114A**, **114B**, **114C**, **114D**. The feed component **122** may be mounted on a rack **129** relative to the deposition head **120**, facilitating movement of a displacement pump **124** to conduct material towards the deposition head **120**. An actuator **140** may be arranged to translate the displacement pump **124** or to translate the deposition head **120** in the desired direction. A nozzle **190** deposits the material onto an article being formed.

(34) Material is configured to be received from the secondary dispensing system **104** at a displacement pump head **125** via a displacement pump control valve **126**. The displacement pump **124** ultimately conducts the material from the displacement pump head **125** towards the deposition head **120**. The control valve **126** advantageously is configured to conduct the material in a first-in, first-out manner; that is, the material is moved to the deposition head **120** in the order in which it was conducted from the secondary dispensing system **104**, retaining its properties and sequential order of dispense. This allows the properties of the printed article to be controlled all the way back to the receiving control valves **110A-D** and the respective reservoirs of the primary dispensing system **102**, improving the particularity of the control of the process and the efficiency of resource consumption.

(35) The displacement pump **124** may comprise a piston pump, with an outer component and an inner component concentric with, the interior of, and/or adjacent to the outer component. As seen in greater detail in the cutaway elevational view of FIG. 4, material may flow or be conducted from the secondary dispensing system **104** in a flow direction **136** in first and second material inlets **131A**, **131B**, corresponding respectively to parts A and B of an uncured or unpolymerized elastomeric material, in an exemplary embodiment a two-part silicone material. The material is conducted in the separate first and second material inlets **131A**, **131B** to facilitate fluid flow uninterrupted by formation of elastomer solids. The actuator **126** is arranged to conduct the material in a first-in, first-out manner through the displacement pump head **125** into a material fill port **132** arranged at the inner component of the displacement pump **124**.

(36) As the material accumulates through the material fill port **132** in the inner component of the displacement pump **124**, piston rods **135** are guided backward in a direction **137** towards the displacement pump head **125**. The piston rods **135** are configured to receive accumulated material in an interior volume thereof without blending or otherwise affecting the order of the accumulated material. As the piston rods **135** are driven outward toward the deposition head **120**, the accumulated material is conducted toward the deposition head **120** in the same order in which it was received at the displacement pump **124** from the secondary dispensing system **104**, such that materials having desired properties will be deposited at the desired locations on the article.

(37) The displacement pump **124** conducts the material towards the deposition head **120** of the

deposition apparatus **106**. As seen in FIGS. 5A and 5B, the deposition head **120** may comprise a dynamic mixing module **150** configured to both actuate and blend the material, such as parts A and B of two-part silicone material, preparatory to depositing the blended material on the substrate to form the article. The deposition head **120** may further comprise a heat transfer module **160**, which facilitates heating or cooling of a block forming the deposition head **120**. A pneumatic suck-back or stop valve **162** is provided proximate a nozzle **190** to achieve a clean cut-off of blended material after a discrete portion of material has been deposited on the article.

(38) In embodiments, the pneumatic suck-back valve **162** may be arranged to define distinct filaments of a plurality of filaments that together form a 3D-printed article. As the deposition head **120** deposits material at different portions of an article, the pneumatic suck-back valve **162** may be actuated to retract or withdraw the material in the deposition head away from the nozzle **190** to facilitate a clean break between the distinct filaments or portions of the article. The deposition thereby avoids the problem of strings of material forming or smearing throughout the article. Whereas existing printheads reverse a flow direction of the material to enact a suck-back by reversing a rotation of an impeller, as discussed in greater detail below, the pneumatic suck-back valve **162** of embodiments of the disclosure utilizes instead a piston arrangement that creates a vacuum effect to withdraw as desired the material away from the nozzle, creating clean breaks to distinguish individual filaments, beads, or layers of printed material.

(39) Additional mixer or valve modules may be advantageously added to the deposition head **120** as desired. For instance, a sonic vibration module **164** is provided proximate the nozzle **190** to provide an additional blending procedure, for example, to reduce a viscosity of the blended material and/or to activate certain additives in the material. The deposition apparatus **106** may advantageously be configured as a modular assembly to be easily disassembled and reassembled for easy cleaning and/or for interchange of individual components based on the needs of a particular task. Where additional vibration, heat transfer, or suck-back modules are required, for example, such may be easily added to and later removed from the deposition head **120**.

(40) Scorelines may be provided at grooves and/or between individual modules in the deposition apparatus **106**, or anywhere along with the additive manufacturing system **100**, where leakage of material from inside the additive manufacturing system **100** is encouraged, the leakage facilitating the expulsion of contaminants from the material. This may be utilized especially in high-purity applications such as producing medical-grade silicones, where contaminants are unsuitable for use with the human body.

(41) Turning to FIG. 5B, the dynamic mixing module **150** may comprise an impeller **180** configured to dynamically mix material obtained from first and second control valves **170A**, **170B**, the first and second control valves **170A**, **170B** arranged to conduct and dispense material from the displacement pump **124** according to a desired final blend of material. A control valve actuator **175** may be arranged to communicate with the controller and to independently actuate the first and second control valves **170A**, **170B** based on the desired material property at a desired location along the article. The first and second control valves **170A**, **170B** may correspond to parts A and B of a two-part silicone material or otherwise can correspond to respective proportioning devices of the secondary dispensing system **104**.

(42) The cutaway perspective view of the deposition apparatus **106** shown in FIG. 6 illustrates the operation of the deposition head **120** on received material. As the material is obtained from an interior volume **133** of the displacement pump **124**, the control valves **170A**, **170B** control the rate and volume at which the material, in this embodiment provided in two parts A and B, may advance toward the dynamic mixing module **150**. As material part A passes the control valve **170A**, it is conducted along a flow direction **171** toward the material part B provided from the control valve **170B**, and then both parts A and B may advance in a combined but unblended flow at a flow direction **172** toward the dynamic mixing module **150**.

(43) The impeller **180** is driven by an actuator **151** to rotate in a direction R1, with protrusions **182**

actuating downward flow of the combined but unblended material parts A and B. As parts A and B flow through dynamic flow paths **183** defined by and between the protrusions **182**, parts A and B are blended to obtain a smooth and consistent material mixture. In an exemplary embodiment, the dynamic mixing module **150** advantageously removes air bubbles from the material, facilitating a more structurally solid, smooth, and aesthetically pleasing formed article. The generally downward flow paths **183** thus conduct the material in a flow direction **173** towards the nozzle **190**. The impeller **180** further is arranged to keep the pressure constant, which improves flow and consistency.

(44) As the blended material passes by a distal end of the impeller **180**, the blended material passes along a flow direction **174** toward the nozzle **190**. A sonic vibration module **164** may provide additional blending and may advantageously reduce the viscosity of the blended material immediately prior to deposition when desired, for example to increase an amount of material deposited at a particular location. In embodiments, certain additives contained in the blended material may be arranged to activate or change properties upon receiving sonic vibrations at the sonic vibration module **164**, thereby enhancing properties of the blended material immediately before deposition.

(45) The pneumatic suck-back or stop valve **162**, as seen more clearly in the cutaway elevational view of FIG. 7A provides a clean cut-off of the blended material, operating to temporarily arrest the flow of the blended material along the flow path **174** by providing a negative pressure that draws blended material back up a distance in the flow channel **184**, thereby preventing unwanted deposition, smearing, or dripping of blended material from the nozzle **190**. As discussed, this may be particularly advantageous when defining distinct filaments of material and/or at distinct points on the printed article.

(46) The pneumatic suck-back valve **162** comprises a plunger **163** configured by operation of a driver to sharply withdraw away from the flow channel **184**, creating a negative pressure in a pneumatic stop line **166** that draws the blended material back upwardly from the nozzle **190**, toward which the blended material otherwise flows due to the actuation of the impeller **180** and in certain configurations due to gravity and back pressure applied from the displacement pump **124**. The negative pressure can be released as the plunger **163** is released by the driver and allowed to return to its original configuration, and the flow of the blended material along the flow path **174** is reestablished.

(47) The arrangement of the pneumatic suck-back valve **162** with the plunger **163** facilitates retraction of material and clean breaks between distinct drops, filaments, or layers without requiring that the actuator **151** reverse its rotation in order to create the retraction. Whereas existing printheads utilize reverse-flow to retract material, the operation of the dynamic mixing module **150** is simplified, and wear and tear on the actuator **151**, and the impeller **180** are minimized, by the provision of the modular pneumatic suck-back valve **162**.

(48) In embodiments, the pneumatic suck-back valve **162** can operate to define apertures in a layer, film, filament, or other deposit of material with high precision. As the deposition apparatus **106** lays down or deposits an otherwise continuous layer or filament of material, the pneumatic suck-back valve **162** may interrupt the deposition for a controlled amount of time to define a gap or aperture in the continuous layer or filament.

(49) The pneumatic suck-back valve **162** may be particularly active and advantageous during stages of deposition where the deposition head **120** is changing a direction along the substrate. For example, the deposition head **120** and the substrate may be arranged to move relative to each other such that the deposition head **120** and the nozzle **190** travel along a surface of the substrate and deposit a continuous filament thereon while additively manufacturing the article. As the deposition head **120** so travels and deposits the continuous filament, the deposition head **120** and the substrate may change a direction of travel, defining an edge or corner portion of the article, or otherwise defining a break in a continuous filament. The pneumatic suck-back valve **162** may, at the moment

that the direction of travel is changed, activate to retract the material flowing through the flow path **174** to effect a clean break distinguishing the filament or material deposited along the surface of the substrate. The pneumatic suck-back valve **162**, as depicted and described is merely exemplary, and other suitable methods, components, and arrangements are envisioned for providing a clean cut-off of material at the nozzle **190**.

(50) The nozzle **190** may comprise any configuration or size for varied and controlled deposition of material. In certain embodiments, the nozzle **190** may have a larger diameter configured to deposit discrete beads or continuous layers of material, while in other embodiments, the nozzle **190** may have a nozzle configured for depositing a continuous filament. The nozzle **190** may have a circular diameter or may comprise a textured aperture allowing for depositions of beads, layers, or filaments having desired textural features. The nozzle **190** may have a dynamic size and/or shape, and can change during deposition to form different sized and shaped deposits. In embodiments, the nozzle **190** may be sized to allow for concentric or coaxial arrangements and flows of different materials, as described in greater detail below.

(51) In embodiments, the nozzle **190** has a same size throughout the course of additively manufacturing a single article. The thread diameters of the layers and/or filaments deposited by the nozzle **190** can be adjusted by controlling the proportions of the print speed, i.e. the flow rate of the material through the deposition head **120**, and the material dispense rate, i.e. the flow rate of material from and through the first and second dispensing systems **102**, **104**. This allows for variable thicknesses and stiffnesses throughout the printed article while continuing the continuous print layers from a single size nozzle **190**.

(52) FIG. 7B illustrates the operation of the heat transfer module **160**. A heat transfer medium or fluid is conducted through at least one heat transfer line **161** along a flow path **166** within a block **155**, defining at least partially the deposition head **120**. The block **155** may be formed from aluminum, stainless steel, Teflon, polymers, or any other suitable material that provides sufficient mechanical support, material purity, and/or heat-transfer characteristics. The material forming the block **155** may advantageously be chosen for minimizing contamination of the material flowing therethrough, this arrangement facilitating the use and production of medical-grade elastomeric articles.

(53) In certain embodiments, the heat transfer fluid may be a refrigerant or other cooling fluid such as cooling water arranged to reduce a temperature of the block **155** and consequently of the material flowing through flow channels **171**, **172**, **173**, **174** defined therein. This may be particularly advantageous for low temperature-curing materials, the cooling effects preventing premature polymerization. In other embodiments, the heat transfer medium may be arranged to add heat to the block **155**, for example, to increase a property such as viscosity of the material flowing through the block **155**.

(54) The heat-transfer module **160** may be controlled manually or by the controller based on information obtained through temperature and/or pressure sensors arranged throughout the deposition apparatus **106**. For example, a downstream temperature of the blended material exiting the dynamic mixing module **150** may trigger, based on a process control scheme according to the calculated properties of the blended material, a need for temperature reduction in the block **155**. The heat-transfer module **160** may communicate with the controller to automatically increase a flow rate of a cooling fluid to decrease the temperature of the block **155**, and consequently of the blended material exiting the dynamic mixing module **150**.

(55) In embodiments, the controller may indicate or determine that a temperature in the block **155** should be increased to, for example, increase temperature and decrease viscosity of the material. This may be beneficial when the flowrate and deposition rate needs to be increased at a particular location for increased thickness or rigidity of particular filaments or segments. In embodiments where the heat-transfer module **160** is a cooling module, the flowrate of cooling heat-transfer fluid or medium (such as cooling water) may be correspondingly decreased; conversely, when the heat-

transfer module **160** is a heating module, the flowrate of heating fluid or power may be correspondingly increased.

(56) When arranged as a heating module, the heat-transfer module **160** may utilize any suitable heating element, including heated fluids arranged to flow through the at least one heat-transfer line **161**, electric heating elements arranged to extend through a thickness of the block **155**, or any other suitable arrangement or component. The heat-transfer module **160** may be arranged to transfer heat from discrete portions of the block **155** or any portion of the deposition head **120** at different times; for example, the heat-transfer module **160** may provide heat upstream of and proximate the impeller **180** while removing heat proximate the nozzle **190**. In other embodiments, the heat-transfer module **160** may remove heat proximate the impeller **180** to prevent any undesired curing in the deposition head **120**. The heat transfer performed by the heat-transfer module **160** may be dynamic and can vary based on the composition of the material flowing through the deposition head **120** at any given time.

(57) Likewise, the pressure of the material may be monitored via pressure sensors at any number of locations in the additive manufacturing system **100**. The controller may be arranged to detect a pressure at an outlet of, for example, the dynamic mixing module **150**, the displacement pump **124**, or the nozzle **190**, with adjustments made at the displacement pump **124**, the control valves **170A**, **170B**, and/or the control valves **114A**, **114B**, **114C**, **114D** of the secondary dispensing system, for example, to maintain a proper pressure of the material throughout the additive manufacturing system **100** and to optimize the flow characteristics of the material.

(58) In an alternative embodiment of the additive manufacturing system **100** shown in FIG. **8**, a deposition apparatus **206** is arranged for coextrusion of material blends having different and discrete properties. Multiple dynamic mixing modules, receiving material having different properties, are arranged in parallel. For instance, a first dynamic mixing module **210** may comprise an impeller **281** housed within a block **211**, blending and actuating a first material in a flow direction **271** towards a nozzle **290**.

(59) A second dynamic mixing module **220** comprises a second impeller **282** housed with a second block **222** and blends and actuates a second material in a flow direction **261** towards the nozzle **290**. As in the deposition apparatus **106** described previously, the impellers **281**, **282** blend elastomeric materials, including, for example, two-part silicone materials and may provide a dynamic mixing of the two material parts to create a smooth, consistent material blend. Each dynamic mixing module **210**, **220** may combine and blend first and second parts A, B of separate silicone materials.

(60) The blended materials from the impellers **281**, **282** are directed in second respective flow directions **272**, **262** towards a coextrusion flange **250**. The coextrusion flange **250** is arranged to have multiple layers with a concentric or coaxial relationship, but in other embodiments may have any suitable configuration of layers and shapes. As the blended materials are conducted through the coextrusion flange **250**, the coextrusion flange **250** directs the blended materials in a third respective flow direction **273**, **263**.

(61) The coextrusion flange **250** may comprise a flange defining a central aperture and an outer aperture, the outer aperture concentric with the central aperture and separated by a flange wall. The material from the second dynamic mixing module **220** may be directed through the outer aperture as the material from the first dynamic mixing module **210** is directed through the inner aperture, for example.

(62) At a distal or nozzle-facing end of the coextrusion flange **250**, the first and second blended materials having different properties are conducted into a combination chamber **251**, in which the blended materials are no longer separated by the flange wall but rather are combined in a concentric and laminar relationship. Because the first and second blended materials are pre-blended when they are arranged in and pass through the combination chamber **251**, no blending of the two blended materials is necessary, but rather the blended materials—one forming an outer layer and

one forming an inner concentric layer, for example—may abut each other and consequently chemically bond to each other after curing, while retaining distinct material properties.

(63) In an embodiment, the first blended material forming the inner layer may be a low-temperature-curing elastomeric material, arranged to cure and solidify rapidly upon deposition. By contrast, the outer layer may be a high-temperature-curing elastomeric material, arranged to cure more slowly upon deposition, so the outer layer may form chemical bonds due to its uncured state with adjacent and subsequently deposited features. This arrangement allows for a bulk of a deposited material, which may be a continuous filament, to be quickly cured such that smearing is minimized, but allowing for sufficient bonding between adjacent filaments to occur for the mechanical strength of the formed article.

(64) After the blended materials have been combined but not blended in the combination chamber **251**, the combined material is conveyed along respective coaxial flow paths **274**, **264** towards the nozzle **290**, where the combined material, owing to the smooth consistency afforded by the dynamic mixing at the impellers **281**, **282**, may be deposited as continuous filaments, discrete points or dots, or as continuous films or layers in an additively manufactured article.

(65) As the additively manufactured article is formed layer by layer, filament by filament, drop by drop, or by combinations of different deposition patterns, the properties of the materials may be dynamically changed, such that a first region of the article may comprise a certain durometer, elasticity, mechanical strength, color, curing rate, and/or other property, while subsequently deposited regions may comprise different durometers, elasticities, mechanical strengths, colors, curing rates, and/or other properties, while being continuously additively manufactured. This arrangement is made possible by the dynamic mixing capabilities of the deposition apparatus **206** and the precision blending of particular materials afforded by the first and secondary dispensing systems and displacement pump as described above, which conducts the materials to the deposition apparatus **206** without necessarily blending the different materials.

(66) For details on the structure provided by the system, method, and components thereof, reference is made to the aforementioned application Ser. No. 16/680,959, which describes discretely and continuously deposited filaments of elastomeric material. The deposited material is described in the preferred embodiment of a plurality of filaments that may abut and are adjacent in x-, y- and z-coordinates/planes to form a definitive article. The filaments are deposited in an uncured or at least partially cured state while retaining the deposited shape. The nozzle and thus the filaments may be adapted for minute filaments or deposited material, such as a 0.1 mm diameter, or other shapes and sizes. In embodiments, nozzles of different shapes and diameters may be provided having any number of different arrangements of shapes, sizes, and concentric or axially arranged layers of material.

(67) While the depicted embodiment describes a system wherein two parallel systems merge to form a combined material having discrete layers with different properties, it will be appreciated that any number of parallel systems may be provided to form combinations of materials having any number of properties. For example, a combined material may be formed from two parallel systems and arranged to have a laminar arrangement, with two sheets of combined but unblended materials, which may be further arranged with and attached to filaments having discrete inner and outer layers formed in another pair of parallel systems.

(68) The parallel systems may be arranged, in certain embodiments, to provide blended material to the coextrusion flange **250** or the combination chamber **251** dynamically. In embodiments, a first parallel system may deliver a first blended material as an inner layer of a continuous filament and a second parallel system may deliver a second blended material as an outer layer of the continuous filament as described above, while a third parallel system may deliver a third blended material to the second blended material in the outer layer according to a dynamic pattern. For example, at times the third blended material may be added and can be mixed to the desired degree with the second blended material as suitable for a resulting property at a particular location on the additively

manufactured article, and at other or subsequent times the flow of the third blended material may be decreased, increased, or discontinued relative to the first and second parallel systems. Any suitable pattern and arrangement of any number of parallel systems, which may be varied by time, by composition, and by how they are arranged relative to each other, is envisioned by embodiments of the disclosure.

(69) In other embodiments, multiple systems may be operated in parallel and/or in series. For instance, in the example depicted above, the first parallel system may blend materials that are themselves a blend of multiple materials and blended according to the embodiments of the disclosure. That is, the first parallel system may blend one or more streams of material that are each blended in a deposition head or dynamic mixing module according to the embodiments. There is no intention to limit the possible configurations of different shapes, properties, and arrangements.

(70) In certain embodiments, the deposition apparatus **206** may produce filaments, points, or layers that are hollow or comprise apertures or other textures. In place of the inner layer of material provided by the impeller **281**, a single outer layer of material may be provided around a flange to produce a hollow interior that reduces the weight and bulk of an additive manufactured article. Gaps, apertures, or other textures may likewise be provided as suitable to vary any number of properties of the deposited material or filament.

(71) In another embodiment of an additive manufacturing system and components thereof shown in FIG. **9**, a deposition apparatus **306** may receive materials according to the previously described embodiments from first and secondary dispensing mechanisms and/or displacement pumps. The deposition apparatus **306** is also equipped with a dynamic mixing module **350** and a pneumatic stop valve **362** to allow for precise depositions of material from nozzle **390**, as described previously. While the nozzle **390** is shown as being arranged downwardly of the dynamic mixing module **350** and pneumatic stop valve **362**, it will be appreciated that the components of the deposition apparatus **306** may take any suitable configuration, shape, or order, as described in greater detail below.

(72) In addition to the deposition apparatus **306**, a deposition substrate **330** is provided to enable dynamic depositions of material. The deposition substrate **330** may provide a movable substrate on which to deposit an article. This arrangement allows for multiple orders, layers, and directions of additive construction, increasing the flexibility of the additive manufacturing process. The deposition substrate **330** may comprise in the depicted embodiment a rotating mandrel **336**, which is configured to rotate in a direction **R9** as the deposition apparatus **306** deposits polymeric material on a surface thereof. As the rotating mandrel **336** rotates in the direction **R9**, not only may the deposition apparatus **306** deposit material in different patterns and orders along the surface of the spinning rotating **336**, but the rotating mandrel **336** may also advantageously overcome the deleterious effects of gravity on the additive manufacturing process.

(73) It has been surprisingly found that as the rotating mandrel **336** rotates in the direction **R9**, the counteraction of centripetal and centrifugal forces acting on the deposited material on the surface of the rotating mandrel **336** prevents unwanted deformation of the article, especially as components thereof grow in height, weight, or other dimensions and as the material is being fully cured. The centripetal and centrifugal forces, operating oppositely in directions pointing inward toward the center of the rotating mandrel **336** and outwardly of the center of the rotating mandrel **336**, operate to prevent the growing article, formed from deposited material, from drooping laterally, collapsing, or otherwise changing its configuration as happens to ubiquitously in existing 3D-printing systems that utilize a rotating build surface. While the rotating mandrel **336** is shown as having a conical configuration, any other shape or configuration may be utilized.

(74) By providing the rotating mandrel **336** in combination with the deposition head **306**, the problems of existing 3D-printing systems, including those that utilize rotating surfaces, requiring the use of cutters, shavers, and drip pans to catch falling material are avoided. Instead, the additive manufacturing system of the disclosure can continuously deposit elastomeric material in filaments,

beads, or layers without the known issues of drooping, deforming, or smearing.

(75) A moving rack **332** is provided on which the rotating mandrel **336** is mounted via an attachment block **331**. An actuator **334**, such as a motor or other suitable device, provides the rotation **R9** of the rotating mandrel **336**. The rotating mandrel **336** may thus advantageously translate along with the moving rack **332** by means of an actuator **335** to further facilitate patterns and/or layers of deposited through the nozzle **390**. In contrast to existing additive manufacturing devices limited to printing only in cartesian coordinates, such as with an ink-jet printer, the additive manufacturing system of embodiments of the disclosure can print in angular coordinates and in any order or pattern necessary. For example, the article deposited and formed on the rotating mandrel **336** may be formed inside-out, with the article being reversed upon removal from the rotating mandrel **336**. The article may also be formed right-side-out, with multiple layers being deposited in a woven fashion.

(76) While in the depicted embodiment the rotating mandrel **336** is moved and translated relative to the nozzle **390** by means of the moving rack **332** and the actuator **335**, in embodiments the deposition apparatus **306** may be configured to move and translate relative to the mandrel **336**. Both the deposition apparatus **306** and the mandrel **336** may move relative to each other as suitable for a particular application. As described above, the ability to move one of the substrate or rotating mandrel **336** and the deposition apparatus **306** relative to each other allows the nozzle **390** to travel along the surface of the rotating mandrel **336** while depositing a continuous filament, bead, or layer of elastomeric material, facilitating an efficient, precise, and continuous build process.

(77) The rotating mandrel **336** may accelerate the curing process of the deposited material by providing a heat-transfer module **360**, wherein heat or refrigeration may be provided. For example, the heat-transfer module **360** may comprise tubing that extends along an inner surface of the rotating mandrel **336** to provide heat to the deposited material for accelerated curing. Alternatively, the heat-transfer module **360** may be configured to provide cooling or refrigeration to the surface of the rotating mandrel **336**, delaying the curing process as additional layers or filaments of material are deposited, thus facilitating improved bonding between distinct filaments, for example, as subsequently deposited filaments have more time to chemically bond with a previously deposited and as-yet uncured filament. In other embodiments, the heat transfer module may apply heating or cooling to a conductive surface of the rotating mandrel **336**.

(78) The heat-transfer module **360** may provide a dynamic heat-transfer profile over a surface of the rotating mandrel **336**. Increased heat transfer may be effected at discrete regions of the rotating mandrel **336**. For example, the heat-transfer module **360** may utilize a heated fluid provided by a pump or other actuator (now shown) to a channel near a surface of the rotating mandrel **336** as indicated by the controller to increase a rate of curing of recently deposited material, while another surface of the mandrel **336** is provided with a lower flow rate of the heated fluid; this may help ensure that the material deposited there can bond to other subsequently deposited filaments.

(79) In a variation, the deposition apparatus **306** may move in relation to the deposition substrate **330**, where both the deposition apparatus **306** and the deposition substrate **330** may move in relation to the other, or both may move. The deposition substrate **330** may translate as a rotating mandrel **336** and translate in a direction, such as along a horizontal direction or plane in the depicted embodiments, according to the desired article. In each instance, the deposition apparatus **306** is metered (and moved, if so arranged), and the deposition substrate **330** is movable according to the CAM system controlling the manufacturing process.

(80) The CAM system may be any suitable system for directing the operation of the first and second dispensing systems, the deposition apparatus, and the deposition substrate according to embodiments of the disclosure. A computer numerical control (CNC) system may also be utilized in embodiments. A controller or control system can be arranged to receive signals from a plurality of sensors arranged throughout the additive manufacturing system. For instance, sensors may be arranged to detect flow rates of material, pressures, temperatures, positions, velocities, and

orientations of particular components.

(81) In embodiments, a sensor can detect the orientation of the deposition substrate relative to the nozzle of the deposition head. A sensor can detect an amount of material in one or more of the vats or reservoirs in the first or primary dispensing system and/or an amount of material accumulated in the proportioning columns of the secondary dispensing system. At least one processor can be configured to direct the operation of the components of the additive manufacturing system, such as the control valves **110A-D**, **114A-D**, the displacement pump **124**, the dynamic mixing module, or the movement of the deposition substrate in rotation and translation, for example. The control system may utilize servo control of various actuators that control the control valves, pumps, deposition apparatus, impellers, pneumatic suck-back valves, and other moving components of the additive manufacturing system to attain an additively manufactured article with regions having different properties at desired locations. The servo control of the components may impart to the system greater accuracy and angular repeatability over other modalities, though the disclosure is not limited to servo control.

(82) Each actuator of the additive manufacturing system that is servo-controlled can be individually and manually tuned to optimize the operation of the system during the additive manufacturing of a particular article. The operation of the servo-controlled actuators that control the dispensing systems, the deposition apparatus, and the deposition substrate can be optimized and adjusted during use based on a process control scheme using a control loop. For example, PID (proportional—integral—derivative) control in any suitable variety such as parallel, series, or expanded form, PI (proportional-integral) control, PD (proportional—derivative) control, proportional control, two-position control, feedback, feedforward, or model-predictive control, combinations thereof, and/or any other suitable process control scheme may be used to control the additive manufacturing system.

(83) The controller may further comprise any suitable utility for converting CAD files or other files into instructions for the additive manufacturing system. The utility for converting CAD files or other files into suitable instructions may account for different properties necessary or desired at different locations along or throughout an additively manufactured article, such as different colors, elasticities, durometers, etc. Based on the different properties desired, the controller may determine an appropriate blend of materials needed to achieve the desired properties and, based on a desired path that the deposition apparatus may trace across a surface of the deposition substrate, an appropriate time for the determined blend of materials to be fed forward the deposition apparatus, so the determined blend arrives at the nozzle at the desired time and location.

(84) The deposition apparatus **306** is shown in a cutaway elevational view in greater detail in FIG. **11**. As in previous embodiments, the dynamic mixing module **350** may comprise an impeller **380**, comprising on an outer surface with protrusions arranged to blend two or more streams of material into a smooth, consistent blended material stream and to drive the material toward the nozzle **390**. A material control valve **370** may advantageously control the volume or flow rate of materials into the dynamic mixing module **350** and material may be conducted into the dynamic mixing module **350** via a material line **340**. A pneumatic suck-back valve **362** may operate similar to previous embodiments wherein a plunger **363** may be withdrawn to create a negative pressure proximate the nozzle **390** to draw blended material back into the deposition apparatus **306**. The operation of the pneumatic suck-back valve **362** serves to mitigate smearing and enable discrete deposits and discrete apertures with a continuous layer or filaments.

(85) The rotating mandrel **336** may be customized to a specific or desired configuration for the final additive-manufactured article. For example, foam or other shapeable and/or additive material may be added onto an outer surface of the rotating mandrel **336** to create a substrate having dynamic or customized dimensions on which the material may be deposited. In other embodiments, the rotating mandrel **336** may comprise or support structures to be integrated into the final article and around which the final article may be additive manufactured. For example, a stiffening matrix

or a textile sleeve may be added to the rotating mandrel **336** and the article additively manufactured thereon and/or therearound. In embodiments, the structures are added to the rotating mandrel **336** and/or to the additively manufactured article during or after the deposition process.

(86) In embodiments, an article may be additively manufactured on a planar substrate and then mounted on the rotating mandrel **336** for further depositions. In an example, a textile material arranged to form an outer layer of an elastomeric liner may be additively manufactured with certain elastomeric structures such as seal-in bands or other frictional features on a planar surface. The textile material is then mounted onto the rotating mandrel **336**, after which a silicone liner may be additively manufactured by the system of the disclosure over the textile material.

(87) Other combinations of pre-processing steps and pre-arranged materials are likewise envisioned. Additionally, the additively manufactured article may be post-processed in further steps; for instance, the additively manufactured article may be removed from the rotating mandrel **336** after the deposition process is complete and further additive manufacturing steps may be performed on a rotating planar surface or a non-rotating build surface.

(88) The configuration of the nozzle **390** may be dynamic and may change by means of an actuator during deposition to build up particular structures or articles. In embodiments, the nozzle **390** may take a horizontal configuration relative to the rotating mandrel **336** near a base of the structure being deposited on the rotating mandrel **336** and may transition to a vertical configuration nearer a top surface of the structure being deposited on the rotating mandrel **336**. In embodiments, the deposition apparatus **306** may be arranged to deposit material in a spiral pattern around the rotating mandrel **336**, attaining a weaving pattern with desired characteristics in terms of strength and elasticity while minimizing the amount of material used. The actuator may also change a configuration of the nozzle shape, such that as a continuous filament is being deposited, a larger filament or different shape of filament may be deposited at certain regions of the article without breaking continuity of the continuous filament. This allow for different properties to be imparted to the additively manufactured article at desired locations.

(89) As seen from FIGS. **12A-12C**, the deposition substrate such as a rotating mandrel **336** may be provided with heat-transfer channels for cooling and for heating. Cooling channels **438** may extend from a backside of the rotating mandrel **436** and through a thickness of the rotating mandrel **336**. The cooling channels **438** may define a “v” shape corresponding to a conical shape of the rotating mandrel **436** and may join near a distal or front end of the rotating mandrel **436**. As such, one of the cooling channels **438** can define an inlet, and another can define an outlet such that a current of cooling media is provided through the cooling channels **438**.

(90) The cooling channels **438** may be connected with an attachment block as described in foregoing embodiments in any suitable manner, and the cooling medium may be any suitable medium, such as cooling water, refrigerant, a gas, or any other suitable medium. The depicted embodiment and description of the cooling channels **438**, as with the depiction of the rotating mandrel as being conical in shape, is merely exemplary, and any suitable configuration may be adopted.

(91) For instance, in embodiments in which the substrate is a rotating planer surface, the cooling channels **438** may be defined through the thickness of the planer surface in any suitable configuration. The cooling channels **438** may have a symmetric or asymmetric configuration and may provide heat transfer in an even and consistent manner or may provide heat transfer in a dynamic manner and at desired locations. Also shown is an attachment **442** at which the rotating mandrel **436** can removably attach to the attachment block by any suitable means. The removable attachment of the rotating mandrel **436** can facilitate the use of differently shaped substrates in the additive manufacturing system for improved customizability of the additively manufactured articles and for operational flexibility.

(92) Also shown are heating channels **440**. As with the cooling channels **338**, the heating channels **440** can be configured to provide heat to a surface of the rotating mandrel **336** in any suitable

configuration. In embodiments, the heating channels **440** can be configured to receive cartridge heating modules. The cartridge heating modules may be controlled by the CAM system to ensure that a desired amount of heat yielding a desired surface temperature is provided, this serving in embodiments to expedite a curing process of the deposited material. The heat provided by each of the cartridge heating modules may be dynamic in that a region of the surface of the rotating mandrel **436** may be heated to promote curing while heat is not applied to another region, for instance to delay a curing process until a subsequent filament is deposited. In other embodiments, the heating channels **440** can be configured to receive a heating medium, such as a heated fluid or to use embedded electrical heating elements.

(93) Turning to FIG. **12C**, a shield **450** may be provided to surround the rotating mandrel **436**. The shield **450** may be arranged with apertures or other means that facilitate currents **452** of heating fluid such as hot air to flow inward and contact a surface **437** of the rotating mandrel **436**. The currents **452** within the shield **450** may further expedite the curing process. Alternatively, the currents **452** may have a temperature lower than a temperature of the deposited material to delay the curing process until subsequent filaments, or layers can be deposited.

(94) FIGS. **13A** and **13B** show an embodiment of a rotating nozzle **490** according to another embodiment of the disclosure. Because the substrate may define an asymmetrical shape, it can be desirable to provide another axis of rotation at the deposition head according to embodiments of the disclosure to ensure that the nozzle deposits material at an angle that is normal to any given point on the surface of the substrate. In the case of the rotating mandrel **436**, the mandrel **436** due to its substantially conical configuration can define a profile or curvature **460**. To allow the nozzle **490** to deposit material at an angle **D13** that is normal to the profile **460**, the nozzle **490** can be a rotating nozzle **490** that extends away from the deposition head on an arm or shaft **494**. The nozzle **490** may be rotated about an axis **A13** by an actuator **480**, which may attach to the deposition head at an attachment **482** comprising a body **481**.

(95) To accommodate the profile **460** without disruption, the deposition substrate **436** and/or the deposition apparatus may comprise an actuator (not shown) configured to change a vertical position of the deposition substrate **436** relative to the deposition apparatus. The actuator allows the nozzle **490** to contact the surface of the deposition substrate **436** at a desired distance suitable for depositing the elastomeric material regardless of the profile **460**, which may otherwise change a distance by which the deposition substrate **436** and the nozzle may be spaced apart. This may be particularly beneficial in instances when the deposition substrate **436** is asymmetric so as to define an asymmetric final article shape.

(96) The deposition apparatus may be further provided with curing means **470** configured to expedite a curing process further. The curing means **470** may be a UV lamp or a heat lamp. By providing the curing means **470** in combination with the deposition apparatus, deposition substrate, and the material blend as described herein, the additively manufactured product may overcome the problems of existing processes which require cutters, shavers, and drip means to address the problem of deposited material being imprecisely deposited and poorly cured in situ to define an article with precise features having desired properties.

(97) By contrast, the additive manufacturing system of the disclosure, by combining the use of a deposition apparatus provided with blends of materials having tailored properties and a deposition substrate according to the embodiments, enables the deposition and additive manufacturing of articles having tailored properties at desired locations while providing a cleaner and continuous process for additive manufacturing of elastomeric articles.

(98) FIGS. **14A-D** show embodiments of a mounting mechanism **500**, **600** configured to cooperate with the deposition substrate. FIGS. **14A** and **14B** show a mounting mechanism **500** according to a first embodiment and configured to cooperate with a rotating mandrel according to embodiments disclosed herein. The mounting mechanism **500** may comprise several arms **502** that function as end effectors and are configured to arrange or place a separate article, such as a non-3D-printed

article, upon the deposition substrate so as to engage with the additively manufactured article.

(99) The mounting mechanism **500** may be used when assembling devices that utilize pre- or post-processing steps to combine an additively manufactured article and a separate article to form a device. An exemplary device formed using a mounting mechanism according to embodiments is a liner in which a textile sleeve is applied to an additively manufactured silicone structure, but the disclosure is not limited to this embodiment.

(100) The end effectors **502** can be arranged about the mounting mechanism **500** to form an enclosure or circumference substantially about the deposition substrate with which the mounting mechanism **500** is configured to cooperate. The end effectors **502** are adjustable to accommodate differently sized deposition substrates and additively manufactured articles built thereon. The end effectors **502** can be rotated or pivoted about at least a first joint **505** to extend the circumference defined by the end effectors **502**, allowing the mounting mechanism **500** to engage with a larger deposition substrate.

(101) The end effectors **502** can be supported relative to a central actuator **507** by arms **509** that extend outwardly from the central actuator **507**. The end effectors **502** can further be configured to pivot about a second joint **511** to maintain a substantially parallel relationship between the end effectors **502** and the deposition substrate. The central actuator **507** can be driven by at least one motor driver **504**. Alternatively, the end effectors **502** can each be actuated independently of each other to enable the mounting mechanism **500** to engage with an asymmetrically or eccentrically shaped deposition substrate.

(102) In use, a separate article such as a textile sleeve is positioned on end effectors **502** to define a circumference relative to the deposition substrate. The mounting mechanism **500**, and the end effectors **502** can be adjusted, so the textile sleeve conforms in size and shape to the deposition substrate. The mounting mechanism **500** can be configured to translate relative to the deposition substrate to position the deposition substrate within a cavity or space defined between the end effectors **502**, so the textile sleeve surrounds and engages the deposition substrate.

(103) In a second embodiment shown in FIGS. **14C-D**, a mounting mechanism **600** likewise comprises end effectors **602** arranged to define a circumference or enclosure around a deposition substrate. The end effectors **602** may support cable actuators **606** that can be routed along a length of the end effectors **602** by routing mechanisms **610**, which may be pulleys, guides, or any other suitable routing mechanism. The cable actuators **606** can be jointly actuated by a central actuator or spool **608** or may be provided with respective actuators.

(104) The cable actuators **606** can serve to move a separate article, such as a non-3D-printed article including a textile sleeve, toward a distal end of the end effectors **602** for placing on the deposition substrate. As with the embodiment of FIGS. **14A-B**, the mounting mechanism **600** may be actuated relative to the deposition substrate such that the separate article mounted on end effectors **602** can substantially surround the deposition substrate, such that as the cable actuators **606** move the separate article toward the distal ends of the end effectors **602**, the separate article can be engaged with and onto the deposition substrate and the article being or recently additively manufactured thereon.

(105) The cable actuators **606** may operate to move the textile sleeve at different speeds at different times to precisely orient the separate article on the deposition substrate in the desired configuration. In an embodiment, the separate article is a textile sleeve to be placed on an elastomeric liner additively manufactured upon the deposition substrate. By arranging the textile sleeve on the elastomeric liner using the mounting mechanism **600**, an automated, and therefore more precise, mounting operation is facilitated, as the imprecisions and risks associated with manually mounting the separate article on the deposition substrate are avoided.

(106) While a rotating mandrel having a conical shape has been shown and described, the deposition substrate may have any suitable configuration based on any desired final article to be additively manufactured. The deposition substrate may be substantially planar, cylindrical,

rectilinear, or any other suitable shape. The deposition substrate need not be symmetric and can define any suitable profile. The additive manufacturing system according to the disclosure can be utilized to additively manufacture any suitable article, including elastomeric breast implants, liners, medical implants such as tubing and seals, joint component replacements, surgical tools, and any other suitable device.

(107) In embodiments where the additive manufacturing system is configured to produce an elastomeric breast implant, the deposition substrate may be provided with a shape and/or rotation configuration that corresponds to a desired shape of the elastomeric breast implant. Because elastomeric breast implants often comprise an upper portion and a lower portion that can define an outer shell inside of which an elastomeric gel, saline solution, or other suitable material can be contained, the deposition substrate of the additive manufacturing system may be configured to additively manufacture a continuous or substantially continuous outer shell from elastomeric material such that the outer shell has desired properties at desired locations. For example, a lower portion arranged to be implanted inwardly can have a greater rigidity or lower elasticity than an upper portion arranged to be implanted outwardly of the lower portion. The upper portion may be additively manufactured to have, for example, greater elasticity in regions to attain a suitable shape that may be asymmetric.

(108) Because elastomeric breast implants are often asymmetric, the deposition substrate can be arranged to move relative to the deposition apparatus, whether by rotation, translation, or otherwise, to define the asymmetric shape of the elastomeric breast implant. In embodiments, the deposition substrate can be a planar surface on which the lower portion of the outer shell is first deposited by the additive manufacturing system as the planar deposition substrate rotates relative to the deposition apparatus.

(109) The additive manufacturing system can be operated so as to impart desired properties such as durometer, elasticity, and other properties at desired points along the lower portion. The deposition apparatus may deposit continuous filaments that have varying properties along a length of the continuous filament and which may chemically bond with adjacent and/or subsequently deposited filaments to define a continuous elastomeric body with desired properties at desired locations.

(110) An upper portion can be built from and on the lower portion to define a continuous outer shell and may comprise filaments that are continuous with filaments that define the lower portion, while nevertheless having different properties to define the upper portion. The filaments may be interspersed with continuously deposited layers and/or drops of an elastomeric material such that the outer shell may define any suitable texture; for example, in embodiments the outer shell may comprise a textured outer surface comprising ridges and corresponding valleys. In other embodiments, outer surfaces of the outer shell may be substantially smooth. A dynamic texture and properties may be defined through a thickness of the outer shell, with a smooth and rigid inner surface of the outer shell configured to encase the silicone gel or saline inside the implant, and with a textured outer surface configured to disrupt capsular tissue after the implant has been placed. The described embodiment is merely exemplary and is not limiting.

(111) In embodiments, the deposition substrate may be an additively manufactured article with dimensions corresponding to the custom dimensions of an article to be printed thereon. For instance, in embodiments wherein the additive manufacturing system is utilized to create an elastomeric liner for a limb residuum, a user's limb dimensions can be measured and used to additively manufacture or otherwise prepare the deposition substrate to match the user's limb. The additively manufactured elastomeric liner can then correspond closely to the user's limb.

(112) By providing an additive manufacturing system, method, and corresponding components for making elastomeric structures according to the disclosure, the limitations of existing additive manufacturing methods—namely, using low quality polymeric materials to facilitate better deposition, the effects of gravity distorting a manufactured article, or the monolithic structure of the article, with a single material having a single set of properties forming the entire structure—are

addressed. The additive manufacturing system provides a dynamic system for selecting from infinitely many combinations of materials and properties to create manufactured articles with dynamic properties at desired regions within the printed article. The deposition apparatus provides for the creation of smooth and consistently blended materials for reliable and consistent properties at desired regions. The system may be arranged for co-extrusion of multiple layers of materials having different properties. A deposition substrate may advantageously provide a dynamic surface on which to build an additive manufactured article.

(113) It is to be understood that not necessarily all objects or advantages may be achieved under an embodiment of the disclosure. Those skilled in the art will recognize that the additive manufacturing system, method, and corresponding components for making elastomeric structures may be embodied or carried out in a manner that achieves or optimizes one advantage or group of advantages as taught herein without necessarily achieving other objects or advantages as may be taught or suggested herein.

(114) The skilled artisan will recognize the interchangeability of various disclosed features. In addition to the variations described herein, other known equivalents for each feature can be mixed and matched by one of skill in this art to construct an additive manufacturing system, method, and corresponding components for making elastomeric structures in accordance with principles of the present disclosure. It will be understood by the skilled artisan that the features described herein may apply to other types of additive manufacturing systems, materials, and articles.

(115) Although this disclosure describes certain exemplary embodiments and examples of an additive manufacturing system, method, and corresponding components for making elastomeric structures, it nevertheless will be understood by those skilled in the art that the present disclosure extends beyond the specifically disclosed embodiments to other alternative embodiments and/or users of the disclosure and obvious modifications and equivalents thereof. It is intended that the scope of the present disclosure should not be limited by the particular disclosed embodiments described above and may be extended to other additive manufacturing systems and methods, and other applications that may employ the features described herein.

Claims

1. A system for additive manufacturing, comprising: a dispensing system having a first reservoir containing a part A of an uncured liquid silicone material and further having a second reservoir containing a part B material of the uncured liquid silicone material, wherein the part A and the part B of the uncured liquid silicone material are curable to form a solid silicone structure; a deposition apparatus comprising a nozzle, a first control valve, and a second control valve, the deposition apparatus arranged to receive the uncured liquid silicone material from the dispensing system; and a deposition substrate configured to receive the uncured liquid silicone material deposited from the nozzle of the deposition apparatus, the deposition substrate having a cylindrical or conical mandrel; a first actuator arranged to rotate the mandrel in a direction about a central axis of the mandrel; a second actuator arranged to translate the mandrel along a rack in a first direction parallel to the central axis of the mandrel; a third actuator configured to translate the deposition apparatus in at least one second direction as the deposition apparatus deposits the uncured liquid silicone material received onto the deposition substrate; and wherein the deposition apparatus further comprises a dynamic mixer for mixing the uncured liquid silicone material; wherein the deposition apparatus is arranged for advancing the part A from the first control valve along a first flow direction toward the part B provided from the second control valve, the deposition apparatus being further arranged for advancing both parts A and B in a combined, but unblended, flow along a second flow direction toward the dynamic mixer; wherein the dynamic mixer comprises an impeller arranged to rotate within a flow channel and mix the uncured liquid silicone material under a constant pressure, the impeller including protrusions configured to actuate downward flow of the material parts A and B

- in the combined, but unblended, flow along the second flow direction toward the dynamic mixer through dynamic flow paths defined by and between the protrusions, the material parts A and B of the uncured liquid silicone material being mixed through the dynamic flow paths; and wherein the deposition apparatus further comprises at least one pneumatic suck-back valve including a plunger configured to withdraw away from the flow channel, creating a negative pressure in a pneumatic stop line that draws the uncured liquid silicone material in the deposition apparatus away from the nozzle to form clean breaks between distinct filaments of the solid silicone structure after a discrete portion of the uncured liquid silicone material has been deposited on the deposition substrate.
2. The system for additive manufacturing of claim 1, wherein the deposition apparatus comprises a sonic vibration module.
 3. The system for additive manufacturing of claim 1, wherein the deposition apparatus further comprises at least one heating and/or cooling element.
 4. The system for additive manufacturing of claim 1, wherein the deposition apparatus comprises a sonic vibration module upstream in the flow channel leading to the nozzle.
 5. The system for additive manufacturing of claim 1, wherein the deposition apparatus comprises at least one temperature sensor and at least one pressure sensor.
 6. The system for additive manufacturing of claim 1, wherein the deposition apparatus includes at least one proportioning device.
 7. The system for additive manufacturing of claim 1, further comprising: a feed component receiving the uncured liquid silicone material from the dispensing system and transferring the uncured liquid silicone material from the dispensing system to the deposition apparatus, the feed component including a displacement pump arranged to transfer the uncured silicone to the deposition apparatus; wherein the displacement pump includes piston rods configured to receive the uncured liquid silicone material without blending or affecting the order of the liquid silicone material being accumulated within the displacement pump, and wherein the uncured liquid silicone material is conducted toward the deposition apparatus when the piston rods are driven toward the deposition apparatus.
 8. The system for additive manufacturing of claim 1, wherein the deposition apparatus is arranged to deposit the uncured liquid silicone material onto the mandrel as the mandrel rotates.
-