

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12419140
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Kim; Tae Gyun et al.

UV light emitting diode

Abstract

A UV light emitting diode includes a substrate having a plurality of holes surrounded by a flat surface, a first conductivity type semiconductor layer disposed on the substrate, a second conductivity type semiconductor layer disposed on the first conductivity type semiconductor layer, an active layer disposed between the first conductivity type semiconductor layer and the second conductivity type semiconductor layer. A distance from the flat surface to the active layer is smaller than a distance from bottom surfaces of the plurality of holes to the active layer. The flat surface is in contact with the first conductivity type semiconductor layer.

Inventors: Kim; Tae Gyun (Gyeonggi-do, KR), Bae; Seon Min (Gyeonggi-do, KR), Lee; Seom Geun (Gyeonggi-do, KR), Lee; Kyu Ho (Gyeonggi-do, KR)

Applicant: SEOUL VIOSYS CO., LTD. (Gyeonggi-do, KR)

Family ID: 1000008821193

Assignee: Seoul Viosys Co., Ltd. (Gyeonggi-do, KR)

Appl. No.: 17/743993

Filed: May 13, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220367753 A1	Nov. 17, 2022

Related U.S. Application Data

us-provisional-application US 63189411 20210517

Publication Classification

Int. Cl.: H10H20/819 (20250101); H10H20/825 (20250101); H10H20/831 (20250101);
H10H20/857 (20250101)

U.S. Cl.:

CPC H10H20/819 (20250101); H10H20/825 (20250101); H10H20/8312 (20250101);
H10H20/857 (20250101);

Field of Classification Search

CPC: H01L (33/20); H01L (33/32); H01L (33/382); H01L (33/62)

USPC: 257/79

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2005/0179130	12/2004	Tanaka	257/730	H01L 21/0237
2013/0069079	12/2012	Kim	N/A	N/A
2016/0056352	12/2015	Koike	438/27	H01L 33/22
2016/0149079	12/2015	Koike	N/A	N/A
2017/0104130	12/2016	Lopez	N/A	N/A
2017/0287698	12/2016	Jain	N/A	H01L 21/0242
2017/0288088	12/2016	Won Cheol	N/A	N/A
2018/0315887	12/2017	Choi et al.	N/A	N/A
2018/0323343	12/2017	Jang et al.	N/A	N/A
2018/0351042	12/2017	Jang et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
112635628	12/2020	CN	N/A
20060030636	12/2005	KR	N/A
20120139855	12/2011	KR	N/A
20160002973	12/2015	KR	N/A
20170094679	12/2016	KR	N/A
20180122215	12/2017	KR	N/A
WO-2019113814	12/2018	WO	N/A

OTHER PUBLICATIONS

English Translation of the International Search Report for PCT/KR2022/007033, Aug. 29, 2022, 2 pages. cited by applicant

Extended European Search Report for European Patent Application No. 22804950.8, Apr. 7, 2025, 9 pages. cited by applicant

Primary Examiner: Richards; Norman D

Assistant Examiner: Dykes; Laura M

Background/Summary

CROSS-REFERENCE OF RELATED APPLICATIONS AND PRIORITY (1) The present application is a non-provisional applications claiming priority to and benefit of U.S. Provisional Application No. 63/189,411 filed May 17, 2021, the disclosure of which is incorporated by reference as if fully set forth herein.

TECHNICAL FIELD

(1) The present disclosure relates to an inorganic semiconductor light emitting diode, and more particularly, to a light emitting diode emitting UV light of 300 nm or less.

BACKGROUND

(2) In general, a light emitting diode emitting UV light within a range of 200 nm to 300 nm can be used in various applications, including a sterilization device, a water or an air purification device, a high-density optical recording device, and an excitation source for a bio-aerosol fluorescence detection system.

(3) Unlike a near-UV light emitting diode or a blue light emitting diode, a light emitting diode that emits relatively more UV light includes a well layer containing Al, such as AlGaIn. Due to a composition of this gallium nitride-based semiconductor layer, a UV light emitting diode has a structure significantly different from that of the blue light emitting diode.

(4) In particular, for the blue light emitting diode, a patterned sapphire substrate is generally used as a growth substrate. A light extraction efficiency of the light emitting diode may be increased by a pattern formed on the sapphire substrate. For the UV light emitting diode, it is necessary to grow a semiconductor layer having a high Al content, such as AlGaIn, which does not grow with a good crystal quality on a conventional patterned sapphire substrate, unlike the semiconductor layer used in the blue light emitting diode.

(5) Accordingly, the conventional UV light emitting diode has been generally manufactured using a sapphire substrate having a flat growth surface, and thus, there is a limit in increasing the light extraction efficiency. Moreover, the conventional UV light emitting diode does not have a favorable crystal quality, and thus, a performance thereof may be easily deteriorated with prolonged use.

DETAILED DESCRIPTION OF THE DISCLOSURE

Technical Problem

(6) Exemplary embodiments of the present disclosure provide a UV light emitting diode with an improved light extraction efficiency.

(7) Exemplary embodiments of the present disclosure provide a UV light emitting diode with a decreased performance degradation even it is used for a long time.

Technical Solution

(8) A UV light emitting diode according to an exemplary embodiment of the present disclosure includes a substrate having a plurality of holes surrounded by a flat surface, a first conductivity type semiconductor layer disposed on the substrate, a second conductivity type semiconductor layer disposed on the first conductivity type semiconductor layer, an active layer disposed between the first conductivity type semiconductor layer and the second conductivity type semiconductor layer. A distance from the flat surface to the active layer is smaller than a distance from bottom surfaces of the plurality of holes to the active layer, and the flat surface is in contact with the first conductivity type semiconductor layer.

(9) Diameters of inlets of the holes may be less than 1 μm , and diameters of the bottom surfaces of the holes may be 500 nm or less.

- (10) The diameters of the inlets of the holes may be in a range of 500 nm to 700 nm.
- (11) Furthermore, a distance between centers of adjacent holes may be 1 μm or more and 3 μm or less.
- (12) In an exemplary embodiment, the holes may be arranged in a honeycomb shape.
- (13) The first conductivity type semiconductor layer may include a plurality of cavities therein, and the plurality of cavities may be disposed on the holes, corresponding to the holes.
- (14) Furthermore, the first conductivity type semiconductor layer may include an AlN layer, and the cavities may be formed in the AlN layer.
- (15) The UV light emitting diode may further include: an n-ohmic contact layer contacting the first conductivity type semiconductor layer; a p-ohmic contact layer contacting the second conductivity type semiconductor layer; an n-pad metal layer electrically connected to the n-ohmic contact layer; a p-pad metal layer electrically connected to the p-ohmic contact layer; an n-bump electrically connected to the n-pad metal layer; and a p-bump electrically connected to the p-pad metal layer, in which the p-pad metal layer may be formed so as to surround the n-pad metal layer.
- (16) The n-bump and the p-bump are disposed in a region over the second conductivity type semiconductor layer.
- (17) The UV light emitting diode may further include a lower insulation layer covering the p-ohmic contact layer and the n-ohmic contact layer, in which the lower insulation layer may have openings exposing the p-ohmic contact layer and the n-ohmic contact layer, and the n-pad metal layer and the p-pad metal layer may be electrically connected to the n-ohmic contact layer and the p-ohmic contact layer through the openings of the lower insulation layer, respectively.
- (18) The UV light emitting diode may further include an upper insulation layer covering the n and p-pad metal layers, in which the upper insulation layer may have openings exposing the n-pad metal layer and the p-pad metal layer, wherein the n-bump and the p-bump may be disposed on the upper insulation layer, and may be electrically connected to the n-pad metal layer and the p-pad metal layer through the openings of the upper insulation layer.
- (19) In the UV light emitting diode according to an exemplary embodiment of the present disclosure, a peak wavelength of an emission spectrum is 280 nm or less, and after driving at room temperature for 1000 hours, a light output is 85% or more compared to an initial light output.
- (20) In some exemplary embodiments, the light output of the UV light emitting diode after driving at room temperature for 1000 hours may be greater than or equal to 90% of the initial light output.
- (21) The UV light emitting diode may include a substrate, a first conductivity type semiconductor layer disposed on the substrate, an active layer disposed on the first conductivity type semiconductor layer, a second conductivity type semiconductor layer disposed on the active layer, an n-ohmic contact layer contacting the first conductivity type semiconductor layer, a p-ohmic contact layer contacting the second conductivity type semiconductor layer, an n-bump electrically connected to the n-ohmic contact layer, and a p-bump electrically connected to the p-ohmic contact layer, in which the substrate may have a hole pattern.
- (22) Furthermore, the first conductivity type semiconductor layer may include an AlN layer, and the AlN layer may have a plurality of cavities therein. The plurality of cavities may be disposed on the holes corresponding to the holes of the hole pattern.
- (23) A portion of the cavities may be disposed in the holes.
- (24) The second conductivity type semiconductor layer may include a p-type GaN layer, in which the p-type GaN layer may have a thickness of 50 nm or less, and the p-ohmic contact layer may be in-ohmic contact with the p-type GaN layer.
- (25) The UV light emitting diode may further include an upper insulation layer covering the n-pad metal layer and the p-pad metal layer. The upper insulation layer may have openings exposing the n-pad metal layer and the p-pad metal layer, and the n-bump and the p-bump may be electrically connected to the n-pad metal layer and the p-pad metal layer through the openings of the upper insulation layer, respectively.

(26) In addition, the upper insulation layer may cover side surfaces of the second conductivity type semiconductor layer and the active layer.

(27) The opening exposing the n-pad metal layer may be disposed near one edge of a mesa, and the opening exposing the p-pad metal layer may be disposed near an opposite edge of the mesa.

Advantageous Effects

(28) According to exemplary embodiments of the present disclosure, it is possible to provide a UV light emitting diode with improved light output and reliability by making a distance from a flat surface of a substrate to an active layer smaller than a distance from bottom surfaces of a plurality of holes to the active layer. In addition, it is possible to provide a UV light emitting diode with improved light output and reliability using holes having a size of 1 μm or less.

Description

BRIEF DESCRIPTION OF DRAWINGS

(1) FIG. 1A is a schematic plan view illustrating a UV light emitting diode according to an exemplary embodiment of the present disclosure.

(2) FIG. 1B is a schematic cross-sectional view taken along line A-A' of its corresponding plan view shown in FIG. 1A.

(3) FIG. 2A is a schematic plan view illustrating a hole pattern formed on a substrate.

(4) FIG. 2B is a planar SEM image showing the hole pattern formed on the substrate according to an exemplary embodiment.

(5) FIG. 2C is a cross-sectional SEM image showing the hole pattern formed on the substrate, according to an exemplary embodiment.

(6) FIG. 3A is a schematic cross-sectional view illustrating a first conductivity type semiconductor layer formed on the substrate.

(7) FIG. 3B is a cross-sectional TEM image showing the first conductivity type semiconductor layer formed on the substrate according to an exemplary embodiment of the present disclosure.

(8) FIG. 3C is a cross-sectional TEM image showing a first conductivity type semiconductor layer formed on the substrate according to another exemplary embodiment of the present disclosure.

(9) FIGS. 4A, 5A, 6A, 7A, 8A, 9A, 10A, and 11A are schematic plan views illustrating a method of manufacturing a UV light emitting diode according to an exemplary embodiment of the present disclosure.

(10) FIGS. 4B, 5B, 6B, 7B, 8B, 9B, 10B, and 11B are schematic cross-sectional views taken along line A-A' of its corresponding plan view shown in FIGS. 4A, 5A, 6A, 7A, 8A, 9A, 10A, and 11A, respectively.

(11) FIG. 4A illustrates forming a hole pattern on an upper surface of a substrate;

(12) FIG. 4B is a cross-sectional view of FIG. 4A along line A-A';

(13) FIG. 5A illustrates growing a first conductivity type semiconductor layer, an active layer, and a second conductivity type semiconductor layer on the substrate;

(14) FIG. 5B illustrates a cross-sectional view of FIG. 5A along line A-A';

(15) FIG. 6A illustrates forming n-ohmic contact layers on bottom surfaces of via holes;

(16) FIG. 6B illustrates a cross-sectional view of FIG. 6A along line A-A';

(17) FIG. 7A illustrates forming a p-ohmic contact layer on the mesa after the n-ohmic contact layer is formed;

(18) FIG. 7B illustrates a cross-sectional view of FIG. 7A along line A-A';

(19) FIG. 8A illustrates forming a lower insulation layer on the mesa M;

(20) FIG. 8B illustrates a cross-sectional view of FIG. 8A along line A-A';

(21) FIG. 9A illustrates forming an n-pad metal layer and a p-pad metal layer on the lower insulation layer;

- (22) FIG. 9B illustrates a cross-sectional view of FIG. 9A;
- (23) FIG. 10A illustrates forming an upper insulation layer on the n-pad metal layer and the p-pad metal layer;
- (24) FIG. 10B illustrates a cross-sectional view of FIG. 10A along line A-A';
- (25) FIG. 11A illustrates forming an n-bump and a p-bump on the upper insulation layer; and
- (26) FIG. 11B illustrates a cross-sectional view of FIG. 11A along line A-A'.
- (27) FIG. 12A is a schematic plan view illustrating a UV light emitting diode according to an exemplary embodiment of the present disclosure.
- (28) FIG. 12B is a schematic cross-sectional view taken along line B-B' of its corresponding plan view shown in FIG. 12A.
- (29) FIGS. 13A, 14A, 15A, 16A, 17A, 18A, 19A, and 20A are schematic plan views illustrating a method of manufacturing a UV light emitting diode according to an exemplary embodiment of the present disclosure.
- (30) FIGS. 13B, 14B, 15B, 16B, 17B, 18B, 19B, and 20B are schematic cross-sectional views taken along line A-A' of its corresponding plan view shown in FIGS. 13A, 14A, 15A, 16A, 17A, 18A, 19A, and 20A, respectively.
- (31) FIG. 13A illustrates growing a first conductivity type semiconductor layer, an active layer, and a second conductivity type semiconductor layer on a substrate.
- (32) FIG. 13B is a cross-sectional view of FIG. 13A along line B-B'.
- (33) FIG. 14A illustrates forming n-ohmic contact layers on the first conductivity type semiconductor layer;
- (34) FIG. 14B illustrates a cross-sectional view of FIG. 14A along line B-B';
- (35) FIG. 15A illustrates after the n-ohmic contact layers **131a** and **131b** are formed, forming a p-ohmic contact layer on the mesa;
- (36) FIG. 15B is a cross-sectional view of FIG. 15A along line B-B';
- (37) FIG. 16A illustrates carrying out an isolation process for dividing the first conductivity type semiconductor layer **123**;
- (38) FIG. 16B is a cross-sectional view of FIG. 16A along line B-B';
- (39) FIG. 17A illustrates forming an n-capping layer and a p-capping layer;
- (40) FIG. 17B is a cross-sectional view of FIG. 17A along line B-B';
- (41) FIG. 18A illustrates forming a lower insulation layer covering the mesa M;
- (42) FIG. 18B is a cross-sectional view of FIG. 18A along line B-B';
- (43) FIG. 19A illustrates forming an n-pad metal layer and a p-pad metal layer on the lower insulation layer;
- (44) FIG. 19B is a cross-sectional view of FIG. 19A along line B-B';
- (45) FIG. 20A illustrates forming an upper insulation layer on the n-pad metal layer and the p-pad metal layer; and
- (46) FIG. 20B is a cross-sectional view of FIG. 20A along line B-B'.
- (47) FIG. 21 is a schematic plan view illustrating a modified example of a mesa of a UV light emitting diode according to an exemplary embodiment of the present disclosure.
- (48) FIG. 22 is a schematic cross-sectional view illustrating a light emitting module according to an exemplary embodiment of the present disclosure.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

(49) Hereinafter, exemplary embodiments will be described in detail with reference to the accompanying drawings. The following exemplary embodiments are provided by way of example so as to fully convey the spirit of the present disclosure to those skilled in the art to which the present disclosure pertains. Accordingly, the present disclosure should not be limited to the specific disclosed forms, and be construed to include all modifications, equivalents, or replacements included in the spirit and scope of the present disclosure. In the drawings, widths, lengths, thicknesses, and the like of elements can be exaggerated for clarity and descriptive purposes. When

an element or layer is referred to as being “disposed above” or “disposed on” another element or layer, it can be directly “disposed above” or “disposed on” the other element or layer or intervening elements or layers can be present. Throughout the specification, like reference numerals denote like elements having the same or similar functions.

(50) Nitride-based semiconductor layers described below may be grown using generally known various methods, and may be grown using technology, for example, metal organic chemical vapor deposition (MOCVD), molecular beam epitaxy (MBE), hydration vapor phase epitaxy (HVPE), or the like. However, in exemplary embodiments described below, it is described that semiconductor layers are grown in a growth chamber using the MOCVD. In a process of growing the nitride-based semiconductor layers, sources introduced into the growth chamber may be generally known sources, for example, TMGa, TEGa, or the like may be used as a Ga source, TMAI, TEAl, or the like may be used as an Al source, TMIIn, TEIn, or the like may be used as an In source, and NH₃ may be used as a N source. However, the inventive concepts are not limited thereto.

(51) FIG. 1A is a schematic plan view illustrating a UV light emitting diode **100** according to an exemplary embodiment of the present disclosure, and FIG. 1B is a schematic cross-sectional view taken along line A-A' of its corresponding plan view shown in FIG. 1A. Meanwhile, FIG. 2A is a schematic plan view illustrating a hole pattern formed on a substrate, FIG. 2B is a planar SEM image showing the hole pattern formed on the substrate, according to an exemplary embodiment, and FIG. 2C is a cross-sectional SEM image showing the hole pattern formed on the substrate, according to an exemplary embodiment. In addition, FIG. 3A is a schematic cross-sectional view illustrating a first conductivity type semiconductor layer formed on the substrate, FIG. 3B is a cross-sectional TEM image showing the first conductivity type semiconductor layer formed on the substrate according to an exemplary embodiment of the present disclosure, and FIG. 3C is a cross-sectional TEM image showing a first conductivity type semiconductor layer formed on the substrate according to another exemplary embodiment of the present disclosure.

(52) Referring to FIG. 1A and FIG. 1B, the UV light emitting diode **100** according to the illustrated exemplary embodiment may include a substrate **21**, a first conductivity type semiconductor layer **23**, an active layer **25**, a second conductivity type semiconductor layer **27**, an n-ohmic contact layer **31**, a p-ohmic contact layer **33**, a lower insulation layer **35**, an n-pad metal layer **37a**, a p-pad metal layer **37b**, an upper insulation layer **39**, an n-bump **41a**, and a p-bump **41b**.

(53) The substrate **21** is not particularly limited as long as it is a substrate capable of growing a nitride-based semiconductor, and may include, for example, a heterogeneous substrate such as a sapphire substrate, a silicon substrate, a silicon carbide substrate, a spinel substrate, or the like. In particular, the substrate **21** may be a sapphire substrate.

(54) The substrate **21** is relatively thick compared to a substrate used in a blue light emitting diode, and for example, it may have a thickness of 200 μm or more, furthermore, 400 μm or more. An upper limit of the thickness of the substrate **21** is not particularly limited, but the upper limit of the thickness may be, for example, 800 μm or less. By using the relatively thick substrate **21**, an amount of ultraviolet rays emitted to the outside may be increased.

(55) As shown in FIG. 1B, the substrate **21** may have a hole pattern including a plurality of holes **21a** formed on a flat surface **21b**. The flat surface **21b** provides a growth site for a nitride semiconductor layer.

(56) The hole pattern of the illustrated exemplary embodiment is different in size from a pattern on a sapphire substrate patterned according to the prior art. The pattern according to the prior art includes a bottom surface and a protrusion, in which the bottom surface provides a main growth site, and a growth layer is merged on the protrusion. In contrast, in the illustrated exemplary embodiment, in the nitride semiconductor layer, the flat surface **21b** provides a main growth site, and a growth layer is merged on the holes **21a**.

(57) As shown in FIG. 2A, the holes **21a** are spaced apart from one another, and the flat surface **21b** is interposed between the holes **21a**. A minimum width of the flat surface **21b** interposed

between the holes **21a** may be 100 nm or more, further, 200 nm or more. The holes **21a** may be arranged, for example, in a honeycomb shape, without being limited thereto. In addition, distances **L1**, **L2**, and **L3** between adjacent holes **21a** may be identical in any direction, but the inventive concepts are not limited thereto. For example, **L1** may be smaller compared to **L2** and **L3**. A minimum distance **L1** between centers of the adjacent holes **21a** may be 1 μm or more, and may be 3 μm or less. When the distance between the centers of the holes **21a** is less than 1 μm , it is difficult to grow the nitride semiconductor layer, and when it exceeds 3 μm , an effect of introducing the hole pattern is lowered, which is not preferable.

(58) The hole **21a** may include an inclined surface and a bottom surface. As shown in FIG. 2A, the bottom surface of the hole **21a** may be formed to have a diameter **D1**, and an inlet of the hole **21a** may be formed to have a diameter **D2**. A region between the diameters **D1** and **D2** is an inclined surface, and growth of the nitride semiconductor layer on the inclined surface is limited.

Meanwhile, the diameter **D1** of the bottom surface of the hole **21a** may have a size of 500 nm or less, and further may have a size of 400 nm or less. For example, the diameter **D1** of the bottom surface of the hole **21a** may be about 300 nm to about 400 nm. However, the inventive concepts are not limited thereto, and there may be no flat bottom surface. That is, the diameter **D1** may be 0 nm. The diameter **D2** may be less than 1 μm , and further may be 700 nm or less. For example, the diameter **D2** may be in a range of about 500 nm to about 700 nm. The inclined surface may be formed as a curved surface, and may be a convex curved surface or a concave curved surface in a direction of a central axis of the hole **21a**. In addition, the inclined surface may be disposed between the flat surface **21b** of the substrate and a light exiting surface that is disposed opposite to the flat surface **21b** and emits light to the outside. However, the present disclosure is not limited to a specific shape of the inclined surface.

(59) By limiting the size of the hole **21a** to 1 μm or less, a crystal layer grown on the flat surface **21b** may be merged over the holes **21a**. The crystal layer may also be grown on the bottom surface of the hole **21a**, but this layer is limited in the hole **21a**. Accordingly, as shown in FIG. 3A, cavities **23h1** and **23h2** may be formed over the holes **21a**.

(60) The patterned sapphire substrate of the prior art includes protrusions spaced apart from one another in an island type, and has a structure in which the protrusions are surrounded by concave portions. In a case of a blue light emitting diode, semiconductor layers can be grown using the concave portions as a growth surface, but in a case of a deep UV light emitting diode, in a conventional patterned sapphire substrate, the crystal layers do not grow well in the concave portion and the crystal layers are not merged well. Thus, many defects such as high density dislocations in the grown nitride semiconductor layers remain.

(61) On the contrary, according to the illustrated exemplary embodiment, by forming the holes **21a** having a small size of less than 1 μm on the upper surface of the substrate **21** and using the flat surface **21b** as the growth surface, it is possible to grow the nitride semiconductor layer for the UV light emitting diode, and to achieve the merge of the crystal layers. Accordingly, the UV light emitting diode may be manufactured using the nitride semiconductor layer having favorable crystal quality. Furthermore, a light extraction efficiency may be improved by using the hole pattern formed on the substrate **21**.

(62) In addition, a height level of the flat surface **21b** used as the growth surface in the present disclosure is higher than that of a flat surface used as the growth surface in the conventional patterned sapphire substrate. In the present disclosure, as the hole may not be completely filled, a semiconductor layer having a high Al content may be easily formed, and it is effective to form the semiconductor layer for the UV light emitting diode with improved crystallinity. In particular, even when the Al content is high, crystal growth is preferentially achieved on the flat surface, thereby improving the crystallinity and thus, a reduction rate of luminous intensity may be decreased even when the light emitting diode is driven for a long time.

(63) In addition, in the patterned sapphire substrate of the prior art, there is a high possibility that

light generated from an active layer is first incident on a surface of the protrusion, and scattering and re-incident into the semiconductor layer due to the curved surface of the protrusion, and thus, the light extraction efficiency may be reduced. However, in a structure of the present disclosure, since there is a high possibility that light generated from the active layer is incident on the flat surface rather than the curved surface of the hole, scattering of light is reduced by the flat surface and the possibility of light entering the inside of the substrate increases, and thus, the light extraction efficiency is increased. Accordingly, as a thickness of the substrate increases in the UV light emitting diode, an amount of light entering the substrate increases, and thus, the luminous intensity may be improved.

(64) In addition, the substrate **21** may have a width (a), a length (b), and a thickness (h), and a luminous density of UV light emitted through the substrate **21** may be increased. A value of the luminous density may be defined as a luminous density ($\text{mW}/\text{mm}^2 \cdot \text{mA}$) = luminous intensity (mW) / (emission area (mm^2) $\times$ current (mA)), in which the emission area (mm^2) may be defined as $(a \cdot b) + 2 \cdot h \cdot (a + b)$. Therefore, in a case of a UV light emitting diode having a width of 0.95 mm, a length of 0.6 mm, and a thickness of 0.4 mm, the luminous density ($\text{mW}/\text{mm}^2 \cdot \text{mA}$) may be 0.083 or more.

(65) The first conductivity type semiconductor layer **23** is disposed on the substrate **21**. The first conductivity type semiconductor layer **23** may include, for example, a buffer layer (**23a** of FIG. 3A) and an n-type AlGaIn layer (**23b** of FIG. 3A). The buffer layer **23a** may have a thickness of 2 μm or more, may have a thickness of about 5 μm or less, and an AlIn material may be used. In an exemplary embodiment, a first AlGaIn layer may include a lower n-type AlGaIn layer (about 2.15 μm) with an Al molar ratio of 0.8 or more, an intermediate AlGaIn layer (1.7 nm) with an Al molar ratio of 0.7 to 0.8, and an upper n-type AlGaIn layer with a thickness of about 66.5 nm. The first conductivity type semiconductor layer **23** is formed of a nitride-based semiconductor having a band gap higher than that of the active layer such that light generated in the active layer passes therethrough. When the gallium nitride-based semiconductor layer is grown on the sapphire substrate **21**, the first conductivity type semiconductor layer **23** may generally include a plurality of layers so as to improve a crystal quality.

(66) According to the illustrated exemplary embodiments, as shown in FIG. 3A, the cavities **23h1** and **23h2** may be formed over the holes **21a**. As shown in FIG. 3B and FIG. 3C, cavities **23h1** and **23h2** having various shapes may be formed according to growth conditions of the buffer layer **23a**, for example, various combinations of two-dimensional growth and three-dimensional growth. The cavities **23h1** and **23h2** are disposed inside the buffer layer **23a**, and an upper surface of the buffer layer **23a** provides a flat growth surface. A first AlGaIn layer **23b** may be grown on the flat growth surface of the buffer layer **23a**.

(67) In cross-section view, the cavity may be disposed in a region between the flat surface **21b** and the flat surface, and may be formed at a location vertically overlapped with a region of the hole **21a**. A width of the cavity may not be greater than a width of the hole **21a**. Since the cavity does not extend to the flat surface **21b**, a bonding strength between the flat surface **21b** and the buffer layer **23a** is maintained, and thus, it is possible to prevent the substrate **21** from being separated from the semiconductor layer in a process of forming a light emitting device by placing electrodes or others, thereafter.

(68) The cavity includes a lower cavity **23h1** and an upper cavity **23h2**, in which both the lower cavity and the upper cavity may be disposed in a region that is vertically overlapped with the region of the hole **21a**, or at least one of the two may be disposed. When forming an imaginary line connecting the flat surfaces **21b**, the lower cavity **23h1** may be disposed so as to be overlapped with the imaginary line. That is, a portion of the lower cavity **23h1** may be disposed in the hole **21a**. Also, when a plurality of lower cavities **23h1** is formed, the plurality of lower cavities **23h1** may be linearly disposed on the imaginary line. An inner region of the lower cavity **23h1** has a different refractive index from those of the semiconductor layers, for example, the buffer layer **23a**

and the substrate **21**, and since the lower cavity **23h1** is disposed on a same line as the flat surface **21b**, light proceeding generally parallel to the flat surface **21b** may be reflected upwardly by the lower cavity **23h1** to improve the light extraction.

(69) The upper cavity **23h2** may be disposed over the lower cavity **23h1**, and the upper cavity may be disposed in the region that is vertically overlapped with the region of the hole **21a**. A maximum width of the upper cavity may be greater than a maximum width of the lower cavity, and the maximum width of the upper cavity may be less than a maximum width of the hole. Moreover, a height of the upper cavity may be greater than that of the lower cavity, preferably greater than a depth of the hole. The height of the upper cavity may be greater than the width of the upper cavity.

(70) The cavities **23h1** and **23h2** may be disposed below half of the thickness of the buffer layer **23a**. The cavities **23h1** and **23h2** may be disposed closer to the surface of the substrate **21** than the active layer **25**, thereby contributing to light scattering, reflection, and emission in a region where the substrate **21** and the semiconductor layer are in contact.

(71) The lower cavity **23h1** may be formed in plurality, and may be disposed to be spaced apart from one another. The plurality of lower cavities **23h1** may have different shapes, and may have irregular shapes. The upper cavity **23h2** may be formed in plurality, and may be disposed to be spaced apart from one another. The plurality of upper cavities **23h2** may have different shapes, and may have irregular shapes. At least one upper cavity **23h2** may have a shape that becomes narrower in a direction closer to the active layer **25**.

(72) Referring back to FIG. **1B**, a mesa **M** is disposed on a partial region of the first conductivity type semiconductor layer **23**. The mesa **M** includes the active layer **25** and the second conductivity type semiconductor layer **27**. In general, after the first conductivity type semiconductor layer **23**, the active layer **25**, and the second conductivity type semiconductor layer **27** are sequentially grown, the mesa **M** is formed by patterning the second conductivity type semiconductor layer **27** and the active layer **25** through a mesa etching process.

(73) The active layer **25** may be a single quantum well structure or a multi-quantum well structure including a well layer and a barrier layer. The well layer may be formed of AlGaIn or AlInGaIn, and the barrier layer may be formed of AlGaIn or AlInGaIn having a band gap wider than the well layer. For example, each well layer may be formed of AlGaIn having an Al molar ratio of about 0.5 with a thickness of about 3.1 nm, and each barrier layer may be formed of AlGaIn having an Al molar ratio of about 0.7 or more with a thickness of about 9 nm or more. In particular, a first barrier layer may be formed to be thicker than other barrier layers with a thickness of 12 nm or more.

Meanwhile, AlGaIn layers having an Al molar ratio of 0.7 to 0.8 in contact with a top and a bottom of each well layer may be disposed in a thickness of about 1 nm, respectively. However, an Al molar ratio of the AlGaIn layer in contact with a last well layer may be 0.8 or more in consideration of the contact with an electron blocking layer.

(74) Meanwhile, the second conductivity type semiconductor layer **27** may include an electron blocking layer and a p-type GaN contact layer. The electron blocking layer prevents electrons from overflowing from the active layer to the second conductivity type semiconductor layer, thereby improving a recombination rate of electrons and holes. The electron blocking layer may be formed of, for example, p-type AlGaIn having an Al molar ratio of about 0.8, and may have a thickness of, for example, about 55 nm to about 100 nm. The electron blocking layer may be formed of a plurality of layers having different Al molar ratios. In the plurality of layers having different Al molar ratios, a thickness of a layer having a high Al molar ratio may be twice or more than that of a layer having a low Al molar ratio. A difference in Al molar ratios of the plurality of layers in the electron blocking layer may be in a range of about 0.05 to about 0.1.

(75) When the difference in Al molar ratios is too large, a lattice defect may occur due to a lattice difference, and non-luminescent recombination may occur due to the defect before holes reach the active layer. When the difference in Al molar ratios is too small, a band gap energy is large, and a movement of holes is lowered, and thus, a radiation efficiency may be lowered. Therefore, by

setting the difference in Al molar ratios in a range of about 0.05 to about 0.1, an efficiency of the hole movement may be facilitated and the radiation efficiency may be increased. Meanwhile, the p-type contact layer may be formed to have a thickness of about 10 nm to about 50 nm, and may be p-Al.sub.xGa.sub.(1-x)N ($0 \leq x < 0.8$). In addition, the p-type contact layer may be formed of a plurality of layers having different Al molar ratios, in which a layer having a higher Al composition ratio among the plurality of layers may be disposed close to the electron blocking layer.

(76) Meanwhile, the p-type GaN contact layer is used for an ohmic contact. The p-type GaN contact layer may absorb light generated in the active layer **25**. The prior art does not solve a drawback of UV absorption by the p-type GaN contact layer. The present disclosure may reduce light absorption of the p-type GaN contact layer by reducing the thickness of the p-type GaN contact layer. In the prior art, the p-type GaN contact layer is generally formed to have a thickness of more than 300 nm, but in the illustrated exemplary embodiment, it may be formed to have a thickness of 50 nm or less, further 30 nm or less. As such, light absorption by the p-type GaN contact layer may be reduced to improve the light extraction efficiency.

(77) In another exemplary embodiment, instead of using the p-type GaN contact layer, an n-type AlGaIn layer may be formed as the contact layer using a tunnel junction. For example, the n-type AlGaIn layer may be tunnel-junctioned to the p-type AlGaIn layer, and the n-type AlGaIn layer may be used instead of the p-type contact layer.

(78) The mesa **M** may have a rectangular shape elongated in one direction, and includes a plurality of via holes **30h** exposing the first conductivity type semiconductor layer **23**. Each of the via holes **30h** may have a concentric circular shape, and may be arranged at substantially equal intervals to one another in a region of the mesa **M**. As well illustrated in FIG. 2A, the via-holes **30h** may be arranged in a honeycomb shape, and thus, it is possible to make intervals between the via-holes **30h** uniform.

(79) The via holes **30h** may have a mirror symmetrical structure with respect to a plane passing in a short axis direction of the mesa **M**. This mirror symmetrical structure assists to spread currents in the mesa **M** to improve a radiation efficiency.

(80) Meanwhile, the n-ohmic contact layers **31** are disposed on the first conductivity type semiconductor layer **23** exposed to the via holes **30h**. The n-ohmic contact layers **31** may be formed by depositing a plurality of metal layers, and thereafter, by alloying the metal layers through a rapid thermal alloy (RTA) process. For example, the n-ohmic contact layers **31** may be alloyed through the RTA process after sequentially depositing Cr/Ti/Al/Ti/Au. Accordingly, the n-ohmic contact layers **31** become alloy layers containing Cr, Ti, Al, and Au.

(81) The n-ohmic contact layers **31** are disposed in the via holes **30h**, respectively. The n-ohmic contact layers **31** are spaced apart from the active layer **25** and the second conductivity type semiconductor layer **27** in the via holes **30h**. In a UV light emitting diode according to the prior art, an n-ohmic contact layer is generally formed to surround the mesa **M** along a perimeter of the mesa **M**, but in the illustrated exemplary embodiment, the n-ohmic contact layer is not disposed around the mesa **M**. Accordingly, it is possible to prevent light emitted through a side surface of the mesa **M** from being blocked by the n-ohmic contact layer **31** or the like.

(82) The p-ohmic contact layer **33** is disposed on the second conductivity type semiconductor layer **27** to be in-ohmic contact with the second conductivity type semiconductor layer **27**. The p-ohmic contact layer **33** may be formed through, for example, the RTA process after depositing Ni/Rh. The p-ohmic contact layer **33** is in-ohmic contact with the second conductivity type semiconductor layer **27**, and covers most of a region over the mesa **M**, for example, 80% or more. Rh has a higher reflectivity to UV rays than Au, which is advantageous for improving the light extraction efficiency. In the present disclosure, since the thickness of the p-type GaN contact layer is reduced to decrease light absorption by the p-type GaN contact layer, so as to reflect light passing through the second conductivity type semiconductor layer **27**, favorable reflection performance of the p-ohmic contact layer **33** is required.

(83) The lower insulation layer **35** covers the mesa **M**, and covers the p-ohmic contact layer **33** and the n-ohmic contact layers **31**. The lower insulation layer **35** also covers the exposed first conductivity type semiconductor layer **23** around the mesa **M** and in the via holes **30h**. Meanwhile, the lower insulation layer **35** has openings **35a** for allowing electrical connection to the n-ohmic contact layers **31** and openings **35b** for allowing electrical connection to the p-ohmic contact layer **33**. The opening **35b** may be formed so as to surround all of the via holes **30h** in a ring shape.

(84) The lower insulation layer **35** may be formed of, for example, SiO.sub.2, without being limited thereto, or may be formed as a distributed Bragg reflector.

(85) Meanwhile, the n-pad metal layer **37a** and the p-pad metal layer **37b** are disposed on the lower insulation layer **35**. In one form, the n-pad metal layer **37a** and the p-pad metal layer **37b** may be formed together in the same process as the same metal layer and disposed on the same level, that is, on the lower insulation layer **35**. The n- and p-pad metal layers **37a** and **37b** may include, for example, Al layers.

(86) The n-pad metal layer **37a** is electrically connected to the n-ohmic contact layers **31** through the openings **35a** of the lower insulation layer **35**. The n-ohmic contact layers **31** are electrically connected to one another by the n-pad metal layer **37a**. The n-pad metal layer **37a** may be disposed within the region of the mesa **M**. The n-pad metal layer **37a** may function as a reflection layer (second reflection layer) that reflects light emitted through the side surface of the mesa **M** in the via hole **30h**, thereby improving a light efficiency of the light emitting diode.

(87) Meanwhile, the p-pad metal layer **37b** may be electrically connected to the p-ohmic contact layer **33** through the opening **35b** of the lower insulation layer **35**. The p-pad metal layer **37b** may cover the opening **35b**, and may surround the n-pad metal layer **37a** in a ring shape. The p-pad metal layer **37b** may be limited in the region over the mesa **M** such that the p-pad metal layer does not cover side surfaces of the mesa **M**.

(88) The upper insulation layer **39** covers the n-pad metal layer **37a** and the p-pad metal layer **37b**. Meanwhile, the upper insulation layer **39** has openings **39a** exposing the n-pad metal layer **37a** and has openings **39b** over the mesa **M** exposing the p-pad metal layer **37b**. The opening **39a** may expose the n-pad metal layer **37a** near one edge of the mesa **M**, and the opening **39b** may expose the p-pad metal layer **37b** near an opposite edge of the mesa **M**.

(89) A plurality of openings **39a** may be arranged, without being limited thereto, or one opening **39a** may be arranged. In addition, although the opening **39b** is illustrated as being continuously formed in a C shape in the drawing, the plurality of openings **39b** may be disposed apart from one another. The upper insulation layer **39** may be formed of, for example, silicon nitride or silicon oxide.

(90) The n-bump **41a** and the p-bump **41b** are placed on the upper insulation layer **39**. The n-bump **41a** covers the openings **39a** and is connected to the n-pad metal layer **37a** exposed through the openings **39a**. The n-bump **41a** is electrically connected to the first conductivity type semiconductor layer **23** through the n-pad metal layer **37a** and the n-ohmic contact layer **31**. Outer edges of the n-bump **41a** and the p-bump **41b** may be disposed over the mesa **M** so as not to cover the side surface of the mesa **M**.

(91) The p-bump **41b** covers the opening **39b** and is connected to the p-pad metal layer **37b** exposed through the opening **39b**. The p-bump **41b** is electrically connected to the second conductivity type semiconductor layer **27** through the p-pad metal layer **37b** and the p-ohmic contact layer **33**.

(92) The n-bump **41a** and the p-bump **41b** may be formed of, for example, Ti/Au/Cr/Au. As shown in FIG. 1, the n-bump **41a** and the p-bump **41b** may be disposed opposite each other, and may occupy about 1/3 of an area of the mesa **M**, respectively. By making the areas of the n-bump **41a** and the p-bump **41b** relatively wide, heat generated in the light emitting diode may be easily dissipated, thereby improving a performance of the light emitting diode.

(93) Furthermore, the openings **39a** and **39b** are covered by the n-bump **41a** and the p-bump **41b**,

and thus, moisture or solder from the outside may be prevented from infiltrating into a device through the openings **39a** and **39b**, thereby improving a reliability thereof.

(94) Meanwhile, although not shown, an anti-reflection layer may be disposed on a light exiting surface of the substrate **21**. The anti-reflection layer may be formed of a transparent insulation layer such as SiO₂ to have a thickness that is an integer multiple of $\frac{1}{4}$ of a wavelength of ultraviolet rays, for example. Alternatively, a bandpass filter in which layers having different refractive indices are repeatedly stacked may be used as the anti-reflection layer.

(95) FIGS. **4A**, **5A**, **6A**, **7A**, **8A**, **9A**, **10A**, and **11A** are schematic plan views illustrating a method of manufacturing a UV light emitting diode according to an exemplary embodiment of the present disclosure, and FIGS. **4B**, **5B**, **6B**, **7B**, **8B**, **9B**, **10B**, and **11B** are schematic cross-sectional views taken along line A-A' of its corresponding plan view shown in FIGS. **4A**, **5A**, **6A**, **7A**, **8A**, **9A**, **10A**, and **11A**, respectively.

(96) First, referring to FIG. **4A** and FIG. **4B**, a hole pattern is formed on an upper surface of a substrate **21**. A plurality of holes **21a** may be formed on the surface of the substrate. The holes **21a** may be formed using photolithography and etching processes, but expensive equipment has to be introduced for the photolithography process so as to form small-sized holes **21a**. In order to avoid this, nano-imprint technology may be used. Sizes, shapes, and arrangements of the holes **21a** are identical to those described above with reference to FIGS. **2A**, **2B**, and **2C**, and thus detailed descriptions thereof will be omitted.

(97) Referring to FIG. **5A** and FIG. **5B**, a first conductivity type semiconductor layer **23**, an active layer **25**, and a second conductivity type semiconductor layer **27** are grown on the substrate **21**.

(98) Since the first conductivity type semiconductor layer **23**, the active layer **25**, and the second conductivity type semiconductor layer **27** are identical to those described above, detailed descriptions thereof will be omitted to avoid redundancy. However, the second conductivity type semiconductor layer **27** may include a semiconductor layer having a band gap smaller than a well layer of the active layer **25**, for example, a GaN layer. In particular, a p-type GaN layer may be used for an ohmic contact. The semiconductor layer having the band gap smaller than the well layer is controlled to have a thickness of 500 nm or less, furthermore, 30 nm or less. In another exemplary embodiment, the p-type GaN layer is omitted, and an n-type AlGaIn layer tunnel-junctioned to the p-type AlGaIn layer may be used instead of the p-type contact layer.

(99) Meanwhile, a mesa **M** is formed by patterning the second conductivity type semiconductor layer **27** and the active layer **25**. The mesa **M** may have a generally elongated rectangular shape, but the inventive concepts are not limited to a specific shape. As the mesa **M** is formed, the first conductivity type semiconductor layer **23** may be exposed along a perimeter of the mesa **M**. Also, a plurality of via holes **30h** are formed in a mesa **M** region. The via holes **30h** expose the first conductivity type semiconductor layer **23**. The via holes **30h** may be spaced apart from one another at substantially equal intervals, and may be arranged, for example, in a honeycomb structure. Furthermore, the via-holes **30h** may be spaced apart from an edge of the mesa **M** by more than the interval between the via-holes **30h**.

(100) Referring to FIG. **6A** and FIG. **6B**, n-ohmic contact layers **31** are formed on bottom surfaces of the via holes **30h**. The n-ohmic contact layers **31** may be alloyed through an RTA process, for example, after sequentially depositing Cr/Ti/Al/Ti/Au. For example, the n-ohmic contact layer **31** may be alloyed through the RTA process at about 965° C. for 30 seconds.

(101) Referring to FIG. **7A** and FIG. **7B**, after the n-ohmic contact layer **31** is formed, a p-ohmic contact layer **33** is formed on the mesa **M**. The p-ohmic contact layer **33** is in ohmic contact with the second conductivity type semiconductor layer **27**. In particular, the p-ohmic contact layer **33** may be in ohmic contact with the p-type GaN layer.

(102) The p-ohmic contact layer **33** may include a reflection metal layer such as Au or Rh. For example, after depositing Ni/Au or Ni/Rh, it may be alloyed through the RTA process. Ni/Au may be heat-treated, for example, at 590° C. for 80 seconds. In contrast, Ni/Rh may be heat-treated at a

relatively lower temperature for a longer time, for example, may be heat-treated at 500° C. for 5 minutes. Rh has a higher reflectivity to UV rays than Au, and thus, the light extraction efficiency may be further increased.

(103) Furthermore, Ni/Rh is advantageous compared to Ni/Au because an interface between the p-type contact layer **27** and the p-ohmic contact layer **33** is formed smoothly to exhibit stable ohmic resistance characteristics. In addition, since the present invention reduces light absorption of the p-type contact layer **27** by reducing a thickness of the p-type GaN contact layer, an amount of light reflected by the p-ohmic contact layer **33** is increased. Accordingly, the light extraction efficiency may be improved by using Rh having a relatively high reflectivity. Referring to FIG. **8A** and FIG. **8B**, a lower insulation layer **35** is formed on the mesa **M**. The lower insulation layer **35** covers side and upper surfaces of the mesa **M**. The lower insulation layer **35** covers the n-ohmic contact layer **31** and the p-ohmic contact layer **33**. Meanwhile, the lower insulation layer **35** has openings **35a** exposing the n-ohmic contact layers **31** and openings **35b** exposing the p-ohmic contact layer **33**.

(104) The opening **35b** of the lower insulation layer **35** may be formed in a ring shape along an entire perimeter of the via holes **30h**. However, the inventive concepts are not limited thereto, and a plurality of openings may be formed so as to expose the p-ohmic contact layer **33**. For example, a portion of the ring-shaped opening **35b** close to the via holes **30h** may be covered with the lower insulation layer **35**, and openings may be formed in portions thereof relatively far from the via holes **30h**.

(105) Referring to FIG. **9A** and FIG. **9B**, an n-pad metal layer **37a** and a p-pad metal layer **37b** are formed on the lower insulation layer **35**. The n-pad metal layer **37a** may be formed so as to cover the via-holes **30h**, and may be electrically connected to the n-ohmic contact layers **31** in the via-holes **30h**. The n-pad metal layer **37a** may also cover inner walls of the via holes **30h**.

(106) The p pad metal layer **37b** may cover the opening **35b**, and may be electrically connected to the p-ohmic contact layer **33** exposed to the opening **35b**. The p-pad metal layer **37b** may be formed in a ring shape so as to surround the n-pad metal layer **37a**. The p-pad metal layer **37b** may be formed so as to cover the side surface of the mesa **M**, or may be formed to be limited in a region over the mesa **M** so as not to block light emitted to the side surface of the mesa **M**.

(107) Referring to FIG. **10A** and FIG. **10B**, an upper insulation layer **39** is formed on the n-pad metal layer **37a** and the p-pad metal layer **37b**. The upper insulation layer **39** may cover the n-pad metal layer **37a** and the p-pad metal layer **37b** and may also cover the side surface of the mesa **M**.

(108) Meanwhile, the upper insulation layer **39** has openings **39a** and **39b** exposing the n-pad metal layer **37a** and the p-pad metal layer **37b**. The openings **39a** expose the n-pad metal layer **37a**, and the openings **39b** expose the p-pad metal layer **37b**. The openings **39a** may be formed near one edge of the mesa **M**, and the opening **39b** may be formed near an opposite edge of the mesa **M** to face the openings **39a**.

(109) Referring to FIG. **11A** and FIG. **11B**, an n-bump **41a** and a p-bump **41b** are formed on the upper insulation layer **39**. The n-bump **41a** is electrically connected to the n-pad metal layer **37a** through the openings **39a**, and the p-bump **41b** is electrically connected to the p-pad metal layer **37b** through the opening **39b**.

(110) The n-bump **41a** and p-bump **41b** may partially cover the side surface of the mesa **M**, respectively, but may be formed so as to be limited a region over the mesa **M**.

(111) According to the illustrated exemplary embodiment, current may be uniformly spread over an entire region of the mesa **M** by forming the via holes **30h** in the mesa **M** region and forming the n-ohmic contact layers **31**. In addition, the light extraction efficiency may be improved by reducing the thickness of the p-type GaN contact layer that absorbs light generated in the active layer **25** and by using Ni/Rh as the p-ohmic contact layer **33**.

(112) Although the via hole **30h** has been illustrated and described as having a circular shape in the previous exemplary embodiment, the shape of the via hole is not limited to the circular shape, and may have various other shapes. The shape and the size of the via hole **30h** affect the size of the

ohmic contact region or the size of the light emitting region. Accordingly, the shape of the via hole **30h** may vary so as to adjust a magnitude of a radiation intensity.

(113) FIG. **12A** is a schematic plan view illustrating a UV light emitting diode according to an exemplary embodiment of the present disclosure, and FIG. **12B** is a schematic cross-sectional view taken along line B-B' of its corresponding plan view shown in FIG. **12A**.

(114) Referring to FIG. **12A** and FIG. **12B**, the UV light emitting diode according to the illustrated exemplary embodiment may include a substrate **121**, a first conductivity type semiconductor layer **123**, an active layer **125**, a second conductivity type semiconductor layer **127**, and n-ohmic contact layers **131a** and **131b**, a p-ohmic contact layer **133**, an n-capping layer **134a**, a p-capping layer **134b**, a lower insulation layer **135**, an n-pad metal layer **137a**, a p-pad metal layer **137b**, an upper insulation layer **139**, an n-bump **141a**, and a p-bump **141b**.

(115) The substrate **121** includes a plurality of holes **121a** surrounded by a flat surface **121b**. Since the substrate **121** is similar to the substrate **21** described with reference to FIGS. **1A** and **1B**, a detailed description thereof will be omitted to avoid redundancy. The first conductivity type semiconductor layer **123** is disposed on the substrate **121**. The first conductivity type semiconductor layer **123** is substantially similar to the first conductivity type semiconductor layer **23** described with reference to FIGS. **1A** and **1B**. In addition, as described with reference to FIG. **3A**, a cavity may be formed in the first conductivity type semiconductor layer **123**. However, in the illustrated exemplary embodiment, edges of an n-type semiconductor layer **123** may be disposed inside a region surrounded by edges of the substrate **121**, and thus, an upper surface of the substrate **121** may be exposed along the edges of the first semiconductor layer **123**. However, the inventive concepts are not limited thereto, and an entire surface of the substrate **121** may be covered with the first conductivity type semiconductor layer **123**. Furthermore, an upper surface of an AlN layer, which is a portion of the first conductivity type semiconductor layer **123**, may be exposed near the edge of the substrate **121**.

(116) A mesa **M** is disposed on a partial region of the first conductivity type semiconductor layer **123**. The mesa **M** includes the active layer **125** and the second conductivity type semiconductor layer **127**. In general, the first conductivity type semiconductor layer **123**, the active layer **125**, and the second conductivity type semiconductor layer **127** are sequentially grown, and thereafter, the mesa **M** is formed by patterning the second conductivity type semiconductor layer **127** and the active layer **125** through a mesa etching process.

(117) Since a stacked structure of the active layer **125** and the second conductivity type semiconductor layer **127** is similar to that described with reference to FIGS. **1A** and **1B**, a detailed description thereof will be omitted to avoid redundancy.

(118) The mesa **M** may have a rectangular external shape elongated in one direction, and includes a groove **130g** exposing the first conductivity type semiconductor layer **123**. The groove **130g** may extend along a longitudinal direction of the mesa **M**. As shown in FIG. **12A**, the groove **130g** may extend from one edge of the mesa **M** toward an opposite edge thereof along the longitudinal direction of the mesa **M**. A mesa region is disposed on both sides of the groove **130g** by the groove **130g**. A length of the groove **130g** exceeds $\frac{1}{2}$ of a length of the mesa **M**. In other words, the length of the groove **130g** is greater than a distance between an inner end of the groove **130g** and the opposite edge of the mesa **M**. Furthermore, the distance between the inner end of the groove **130g** and the opposite edge of the mesa **M** may be smaller than a width of the mesa region disposed on both sides of the groove **130g**.

(119) The groove **130g** may have a linear shape, and the mesa **M** may have a symmetrical structure with respect to a straight line passing through a center of the light emitting diode and parallel to the groove **130g**.

(120) Meanwhile, corners of the mesa **M** may have curved shapes. The edge of the mesa **M** may include a straight region and curved regions disposed on both sides thereof. By forming the corners of the mesa **M** to be curved, it is possible to prevent light from being condensed at the corner

portion and thereby being lost due to light absorption.

(121) Meanwhile, the n-ohmic contact layer **131a** is disposed on the first conductivity type semiconductor layer **123** exposed by the groove **130g**. The n-ohmic contact layer **131b** is disposed on the first conductivity type semiconductor layer **123** exposed along a perimeter of the mesa **M**. The n-ohmic contact layer **131a** may be connected to the n-ohmic contact layer **131b**, but the inventive concepts are not limited thereto. The n-ohmic contact layers **131a** and **131b** may be spaced apart from the mesa **M** to surround the mesa **M**.

(122) Materials and methods of forming the n-ohmic contact layers **131a** and **131b** are similar to those of forming the n-ohmic contact layers **31** described with reference to FIGS. **1A** and **1B**, and thus, detailed descriptions thereof will be omitted to avoid redundancy.

(123) The p-ohmic contact layer **133** is disposed on the second conductivity type semiconductor layer **127** to be in ohmic contact with the second conductivity type semiconductor layer **127**. The p-ohmic contact layer **133** may be formed using, for example, Ni/Rh or Ni/Au. The p-ohmic contact layer **133** is in ohmic contact with the second conductivity type semiconductor layer **127** and covers most of a region over the mesa **M**, for example, 80% or more.

(124) The n-capping layer **134a** may cover upper surfaces and side surfaces of the n-ohmic contact layers **131a** and **131b**. The p-capping layer **134b** may cover the upper and side surfaces of the p-ohmic contact layer **133**. The n-capping layer **134a** and the p-capping layer **134b** prevent the n-ohmic contact layers **131a** and **131b** and the p-ohmic contact layer **133** from being damaged by etching, oxidation, or the like, respectively. The n-capping layer **134a** and the p-capping layer **134b** may be formed of a same metal in a same process. For example, the n-capping layer **134a** and the p-capping layer **134b** may be formed of Ti/Au/Ti.

(125) The lower insulation layer **135** covers the mesa **M**, and covers the n-capping layer **134a** and the p-capping layer **134b**. The lower insulation layer **135** also covers the first conductivity type semiconductor layer **123** exposed around the mesa **M** and in the groove **130g**. Furthermore, the lower insulation layer **135** may cover a portion of the substrate **121** exposed around the first conductivity type semiconductor layer **123**. Meanwhile, the lower insulation layer **135** has openings **135a** for allowing electrical connection to the n-ohmic contact layers **131a** and **131b** and openings **135b** for allowing electrical connection to the p-ohmic contact layer **133**. The opening **135a** may have a shape similar to those of the n-ohmic contact layers **131a** and **131b** or the n-capping layer **134a**. That is, the opening **135a** surrounds the mesa **M** and also extends into the groove **130g**. A width of the opening **135a** may be smaller than that of the n-capping layer **134a**, and thus, the first conductivity type semiconductor layer **123** may not be exposed through the opening **135a**. Meanwhile, the opening **135b** is disposed in the region over the mesa **M**, and exposes the p-capping layer **134b**. A plurality of openings **135b** may be disposed on the p-capping layer **134b**. In particular, the openings may be symmetrically disposed on both sides of the groove **130g**.

(126) The lower insulation layer **135** may be formed of, for example, SiO₂, without being limited thereto, and may be formed as a distributed Bragg reflector. In particular, the lower insulation layer **135** may be formed so as to constitute an omni-directional reflector (ODR). For example, the lower insulation layer **135** may be formed of about 10,000 Å of SiO₂.

(127) Meanwhile, the n-pad metal layer **137a** and the p-pad metal layer **137b** are disposed on the lower insulation layer **135**. In one form, the n-pad metal layer **137a** and the p-pad metal layer **137b** may be formed together in the same process with the same metal layer and disposed on a same level, that is, on the lower insulation layer **135**. The n-pad and p-pad metal layers **137a** and **137b** may include, for example, an Al layer.

(128) The n-pad metal layer **137a** is electrically connected to the n-ohmic contact layers **131a** and **131b** through the opening **135a** of the lower insulation layer **135**. The n-pad metal layer **137a** may directly contact the n-capping layer **134a** through the opening **135a** of the lower insulation layer **135**. The n-pad metal layer **137a** may cover most region of the mesa **M**, and may also cover a

region around the mesa M. The n-pad metal layer **137a** may form the ODR together with the lower insulation layer **135**.

(129) Meanwhile, the p-pad metal layer **137b** may be electrically connected to the p-ohmic contact layer **133** through the opening **135b** of the lower insulation layer **135**. The p-pad metal layers **137b** may cover each of the openings **135b**. Each of the p-pad metal layers **137b** may be surrounded by the n-pad metal layer **137a**. The p-pad metal layers **137b** may be limited in the region over the mesa M. In the illustrated exemplary embodiment, all side surfaces of the mesa M are covered with the n-pad metal layer **137a**. Accordingly, it is possible to prevent light loss from occurring at the side surfaces of the mesa M.

(130) The upper insulation layer **139** covers the n-pad metal layer **137a** and the p-pad metal layer **137b**. However, the upper insulation layer **139** may have openings **139a** exposing the n-pad metal layer **137a** and openings **139b** exposing the p-pad metal layer **137b**. The opening **139a** may expose the n-pad metal layer **137a** near one edge of the mesa M, and the openings **139b** may expose the p-pad metal layer **137b** near the opposite edge of the mesa M. The openings **139a** and **139b** may be symmetrically disposed with respect to a line passing through the groove **130g**, but the inventive concepts are not limited thereto.

(131) The upper insulation layer **139** may be formed of, for example, silicon nitride or silicon oxide.

(132) The n-bump **141a** and the p-bump **141b** are disposed on the upper insulation layer **139**. The n-bump **141a** covers the openings **139a** and is connected to the n-pad metal layer **137a** exposed through the openings **139a**. The n-bump **141a** is electrically connected to the first conductivity type semiconductor layer **123** through the n-pad metal layer **137a** and the n-ohmic contact layers **131a** and **131b**. The n-bump **141a** and the p-bump **141b** may partially cover the side surfaces of the mesa M.

(133) The p-bump **141b** covers the openings **139b** and is connected to the p-pad metal layer **137b** exposed through the openings **139b**. The p-bump **141b** is electrically connected to the second conductivity type semiconductor layer **127** through the p-pad metal layer **137b** and the p-ohmic contact layer **133**.

(134) The n-bump **141a** and p-bump **141b** may include Ti/Au, and may be formed of, for example, Ti/Au/Cr/Au or Ti/Ni/Ti/Ni/TiNi/Ti/Au. As shown in FIG. 12A, the n-bump **141a** and the p-bump **141b** may be disposed opposite each other, and may occupy about $\frac{1}{3}$ of an area of the mesa M, respectively. By making the areas of the n-bump **141a** and the p-bump **141b** relatively wide, heat generated in the light emitting diode may be easily dissipated, thereby improving a performance of the light emitting diode.

(135) Furthermore, the openings **139a** and **139b** are covered by the n-bump **141a** and the p-bump **141b**, and thus, moisture or solder from the outside may be prevented from infiltrating into the openings **139a** and **139b**, thereby improving reliability.

(136) Meanwhile, although not shown, an anti-reflection layer may be disposed on a light exiting surface of the substrate **121**. The anti-reflection layer may be formed of a transparent insulation layer such as SiO₂ to have a thickness that is an integer multiple of $\frac{1}{4}$ of a wavelength of ultraviolet rays, for example. Alternatively, a bandpass filter in which layers having different refractive indices are repeatedly stacked may be used as the anti-reflection layer.

(137) FIGS. 13A, 14A, 15A, 16A, 17A, 18A, 19A, and 20A are schematic plan views illustrating a method of manufacturing a UV light emitting diode according to an exemplary embodiment of the present disclosure, and FIGS. 13B, 14B, 15B, 16B, 17B, 18B, 19B, and 20B are schematic cross-sectional views taken along line A-A' of its corresponding plan view shown in FIGS. 13A, 14A, 15A, 16A, 17A, 18A, 19A, and 20A, respectively.

(138) Referring to FIG. 13A and FIG. 13B, first, a first conductivity type semiconductor layer **123**, an active layer **125**, and a second conductivity type semiconductor layer **127** are grown on a substrate **121**.

(139) The substrate **121** includes a plurality of holes **121a** surrounded by a flat surface **121b**. Since the substrate **121**, the first conductivity type semiconductor layer **123**, the active layer **125**, and the second conductivity type semiconductor layer **127** are identical to those described above, detailed descriptions thereof will be omitted to avoid redundancy.

(140) Meanwhile, a mesa **M** is formed by patterning the second conductivity type semiconductor layer **127** and the active layer **125**. The mesa **M** may have a generally elongated rectangular shape, but the inventive concepts are not limited to a specific shape. As the mesa **M** is formed, the first conductivity type semiconductor layer **123** may be exposed along a perimeter of the mesa **M**. In addition, a groove **130g** is formed in a mesa **M** region. The groove **130g** may extend from one edge toward an opposite edge along a longitudinal direction of the mesa **M**. An inner end of the groove **130g** may be disposed near the opposite edge. The mesa regions disposed on both sides of the groove **130g** may be identical to one another, and a width of each of the mesa regions may be greater than or equal to a distance between the inner end of the groove **130g** and the opposite edge of the mesa **M**.

(141) Referring to FIG. **14A** and FIG. **14B**, n-ohmic contact layers **131a** and **131b** are formed on the first conductivity type semiconductor layer **123**. The n-ohmic contact layers **131a** and **131b** may be formed by, for example, sequentially depositing Cr/Ti/Al/Ti/Au, and thereafter being alloyed using an RTA process. For example, the n-ohmic contact layers **131a** and **131b** may be alloyed through the RTA process at about 965° C. for 30 seconds. The n-ohmic contact layer **131a** is formed on the first conductivity type semiconductor layer **123** exposed by the groove **130g**, and the n-ohmic contact layer **131b** is formed on the first conductivity type semiconductor layer **123** exposed around the mesa **M**. The n-ohmic contact layer **131a** may extend from the n-ohmic contact layer **131b**. By continuously forming the n-ohmic contact layer **131a** and the n-ohmic contact layer **131b**, current spreading may be aided. However, the inventive concepts are not limited thereto, and the n-ohmic contact layer **131a** may be spaced apart from the n-ohmic contact layer **131b**.

(142) Referring to FIG. **15A** and FIG. **15B**, after the n-ohmic contact layers **131a** and **131b** are formed, a p-ohmic contact layer **133** is formed on the mesa **M**. The p-ohmic contact layer **133** is in ohmic contact with the second conductivity type semiconductor layer **127**. In particular, the p-ohmic contact layer **133** may be in ohmic contact with a p-type GaN layer.

(143) The p-ohmic contact layer **133** may include a reflection metal layer such as Au or Rh. For example, after depositing Ni/Au or Ni/Rh, it may be alloyed through the RTA process.

(144) Referring to FIG. **16A** and FIG. **16B**, an isolation process for dividing the first conductivity type semiconductor layer **123** is carried out. That is, the first conductivity type semiconductor layer **123** between adjacent light emitting diode regions is removed to expose an upper surface of the substrate **121**. By adding the isolation process, singularization of the light emitting diodes may be aided.

(145) Referring to FIG. **17A** and FIG. **17B**, an n-capping layer **134a** and a p-capping layer **134b** are formed. The n-capping layer **134a** covers upper and side surfaces of the n-type ohmic contact layers **131a** and **131b**, and the p-capping layer **134b** covers upper and side surfaces of the p-type ohmic contact layer **133**. The n-capping layer **134a** and the p-capping layer **134b** may be formed of, for example, Ti/Au/Ti.

(146) Referring to FIG. **18A** and FIG. **18B**, a lower insulation layer **135** covering the mesa **M** is formed. The lower insulation layer **135** covers side and upper surfaces of the mesa **M**. The lower insulation layer **135** also covers the n-capping layer **134a** and the p-capping layer **134b**. The lower insulation layer **135** may cover a side surface of the first conductivity type semiconductor layer **123**, and may partially cover the substrate **121** exposed around the first conductivity type semiconductor layer **123**. Meanwhile, the lower insulation layer **135** has openings **135a** and **135b** exposing the n-capping layer **134a** and the p-capping layer **134b**.

(147) The opening **135a** of the lower insulation layer **135** exposes the n-capping layer **134a**, and the opening **135b** exposes the p-capping layer **134b**. A plurality of openings **135b** may be formed

on the p-capping layer **134b**. As illustrated, the openings **135b** may be symmetrically disposed on both sides of the groove **130g**.

(148) Referring to FIG. **19A** and FIG. **19B**, an n-pad metal layer **137a** and a p-pad metal layer **137b** are formed on the lower insulation layer **135**. The n-pad metal layer **137a** may be electrically connected to the n-capping layer **134a** through the opening **135a**, and the p-pad metal layer **137b** may be electrically connected to the p-capping layer **134b** through the opening **135b**. As illustrated, the n-pad metal layer **137a** may surround the p-pad metal layers **137b**.

(149) The n-pad metal layer **137a** may cover the opening **135a**, and the p-pad metal layer **137b** may cover the opening **135b**. In addition, the n-pad metal layer **137a** may continuously cover the side surface of the mesa **M**, and thus, light reflectivity may be improved on the side surface of the mesa **M**.

(150) Referring to FIG. **20A** and FIG. **20B**, an upper insulation layer **139** is formed on the n-pad metal layer **137a** and the p-pad metal layer **137b**. The upper insulation layer **139** may cover the n-pad metal layer **137a** and the p-pad metal layer **137b** and may also cover an edge of the first conductivity type semiconductor layer **123**. The upper insulation layer **139** may also cover a portion of the upper surface of the substrate **121**.

(151) The upper insulation layer **139** has openings **139a** and **139b** exposing the n-pad metal layer **137a** and the p-pad metal layer **137b**. The openings **139a** expose the n-pad metal layer **137a**, and the openings **139b** expose the p-pad metal layer **137b**. The openings **139a** may be formed near one edge of the mesa **M**, and the openings **139b** may be formed near an opposite edge of the mesa **M** to face the openings **139a**.

(152) Subsequently, as shown in FIGS. **12A** and **12B**, an n-bump **141a** and a p-bump **141b** are formed on the upper insulation layer **139**. The n-bump **141a** is electrically connected to the n-pad metal layer **137a** through the openings **139a**, and the p-bump **141b** is electrically connected to the p-pad metal layer **137b** through the opening **139b**.

(153) The n-bump **141a** and p-bump **141b** may partially cover the side surface of the mesa **M**, respectively, but may be formed to be limited in a region over the mesa **M**.

(154) According to the illustrated exemplary embodiment, by forming the groove **130g** within the mesa **M** region and forming the n-ohmic contact layers **131a** and **131b** around the mesa **M** and in the groove **130g**, current may be uniformly spread over an entire region of the mesa **M**.

(155) FIG. **21** is a schematic plan view illustrating a modified example of a mesa of a UV light emitting diode according to an exemplary embodiment of the present disclosure.

(156) Referring to FIG. **21**, a groove **130g** extends from one edge of the mesa **M** toward an opposite edge in a longitudinal direction. A distance between an inner end of the groove **130g** and the opposite edge of the mesa **M**, that is, a difference **W1** between a total length of the mesa **M** and a length of the groove **130g** may be less than or equal to a width **W2** of each mesa region which is disposed on both sides of the groove **130g**. Moreover, the length of the groove **130g** is greater than **W1**, and thus, exceeds $\frac{1}{2}$ of the length of the mesa **M**. Meanwhile, an area **A1** of the mesa **M** between the groove **130g** and the opposite edge of the mesa **M** may be smaller than an area **A2** of each mesa region disposed on both sides of the mesa **M**. That is, a total area **2A2** of the mesa regions disposed on both sides of the mesa **M** may exceed $\frac{1}{2}$ of a total area of the mesa.

(157) FIG. **22** is a schematic cross-sectional view illustrating a light emitting module according to an exemplary embodiment of the present disclosure.

(158) Referring to FIG. **22**, the light emitting module may include a circuit board **201**, a light emitting diode **200**, bonding layers **203a** and **203b**, and a cover **205**. Since the light emitting diode **200** is identical to the light emitting diode described with reference to FIGS. **12A** and **12B**, a detailed description thereof will be omitted. The light emitting diode **100** described with reference to FIGS. **1A** and **1B** may be used.

(159) The light emitting diode **200** may be flip-bonded on the circuit board **201** such that the substrate **121** is disposed on an upper surface thereof to form a light exiting surface. The light

emitting diode **200** may be bonded to the circuit board **201** through the bonding layers **203a** and **203b**.

(160) The cover **205** covers the light emitting diode **200**. The cover **205** may be formed of a material having transmittance to ultraviolet rays. The cover **205** in a form of quartz or glass may be disposed over to be spaced apart from the light emitting diode **200**, or in contrast, as shown in FIG. **22**, the cover **205** formed of a silicone material may be disposed to cover upper and side surfaces of the light emitting diode **200**. When the silicone material is used, an external shape may be a dome-type shape having a curved surface so as to facilitate light extraction. To prevent damage to the silicone material by ultraviolet rays, the silicone material may be a fluorine-based material, and may include a carbon material together. A content of fluorine compared to carbon may be in a range of 10-35 atomic %: 65-90 atomic %, and in a case of having such a fluorine content, it is possible to effectively extract 200 nm to 300 nm of UV light while maintaining an effect of preventing silicone damage. In the above case, since an active layer **125** generating UV light is disposed closer to a flat surface **121b** of a substrate **121**, a possibility of light first contacting and entering the flat surface **121b** increases. Accordingly, a decrease in luminous intensity due to scattering of light generated at a boundary between the substrate **121** and the semiconductor layer is prevented, and the light extraction efficiency is increased.

EXAMPLE

(161) According to the prior art, a UV light emitting diode of a Comparative Example was manufactured using a flat sapphire substrate having no hole pattern as a growth substrate, and, a UV light emitting diode of an Inventive Example was manufactured using a sapphire substrate having a hole pattern as a growth substrate. Both Comparative Example and Inventive Example were fabricated using 2-inch wafers. In an exemplary embodiment, a hole pattern was formed with a target that a diameter of the hole (D2) was 800 nm (± 40 nm), and a depth of the hole was 200 nm (± 50 nm). For the Comparative Example, five samples fabricated on a same wafer were prepared, and for the Inventive Example, nine samples fabricated on a same wafer were prepared. The samples of these Comparative Example and Inventive Example were driven at room temperature for 1000 hours to measure changes of light outputs, threshold voltages, and turn-on voltages over time with respect to an initial light output. The initial light output means radiant power measured within 24 hours after driving the samples. The initial light output was expressed as 100%, and the changes over time at 250-hour intervals were summarized in Tables 1 and 2 below as a percentage of an initial value. The initial light outputs and turn-on voltages of the samples of the Inventive Example were relatively higher than those of the samples of the Comparative Example, and the initial threshold voltages of the samples of the Inventive Example were relatively lower than those of the samples of the Comparative Example.

(162) TABLE-US-00001

	TABLE 1	250 hours	500 hours	No PO	VF	TOV(@1 uA)	PO	VF	TOV(@1 uA)
Inventive 1	98.2%	98.4%	99.4%	98.9%	98.2%	98.9%	Example 2	96.4%	96.9%
	98.7%	95.4%	96.7%	98.3%	3	91.5%	96.7%	97.4%	91.5%
	96.6%	96.8%	4	89.7%	96.2%	91.8%			
	89.2%	95.9%	93.2%	5	95.8%	97.7%	96.3%	95.2%	97.6%
	95.6%	6	97.0%	96.9%	99.8%	96.0%			
	96.7%	99.7%	7	90.5%	98.2%	100.1%	89.9%	98.0%	99.9%
	92.9%	96.9%							
	99.8%	9	94.3%	100.0%	98.9%	94.2%	97.7%	98.4%	Average
	94.2%	97.6%	98.0%	93.7%	97.1%				
	97.8%	Minimum	89.7%	96.2%	98.0%	89.2%	95.9%	93.2%	Maximum
	98.2%	100.0%	91.8%						
	98.9%	98.2%	99.9%	Comparative 1	89.6%	95.8%	100.1%	86.1%	95.6%
	100.9%	Example 2	85.8%						
	95.8%	100.9%	78.8%	95.6%	100.8%	3	86.7%	95.8%	100.9%
	81.2%	95.6%	101.0%	4	85.5%				
	95.7%	100.7%	78.7%	95.5%	100.8%	5	84.1%	95.8%	100.9%
	77.5%	95.7%	100.8%	Average					
	86.3%	95.8%	100.8%	80.5%	95.6%	100.9%	Minimum	84.1%	95.7%
	100.7%	77.5%	95.5%						
	100.8%	Maximum	89.6%	95.8%	100.9%	86.1%	95.7%	101.0%	

(163) TABLE-US-00002

	TABLE 2	750 hours	1000 hours	No PO	VF	TOV(@ 1 uA)	PO	VF	TOV(@1 uA)
Inventive 1	96.4%	98.2%	98.5%	95.9%	98.2%	98.6%	Example 2	94.2%	96.7%
	98.2%	94.5%	96.7%	97.5%	3	89.5%	96.6%	95.5%	90.0%
	96.7%	95.9%	4	87.3%	95.9%	93.3%			

87.4% 96.0% 94.2% 5 93.2% 97.6% 95.2% 93.2% 97.7% 95.2% 6 93.9% 96.6% 99.5% 95.0%
 96.7% 99.5% 7 88.9% 98.1% 99.8% 89.5% 98.0% 99.9% 8 92.0% 96.8% 99.5% 92.4% 96.9%
 99.5% 9 92.1% 97.7% 98.0% 92.8% 97.8% 98.0% Average 91.9% 97.1% 97.5% 92.3% 97.2%
 97.6% Minimum 87.3% 95.9% 93.3% 87.4% 96.0% 94.2% Maximum 96.4% 98.2% 99.8% 95.9%
 98.2% 99.9% Comparative 1 84.8% 95.7% 101.0% 81.9% 95.7% 101.0% Example 2 78.6% 95.7%
 100.9% 78.6% 95.7% 101.0% 3 80.6% 95.7% 101.2% 79.3% 95.7% 101.1% 4 78.3% 95.6%
 94.7% 77.5% 95.6% 19.7% 5 77.3% 95.7% 101.1% 77.1% 95.7% 101.2% Average 79.9% 95.7%
 99.7% 78.9% 95.7% 84.8% Minimum 77.3% 95.6% 94.7% 77.1% 95.6% 19.7% Maximum 84.8%
 95.7% 101.2% 81.9% 95.7% 101.2%

(164) Referring to Tables 1 and 2, the samples of the Inventive Example exhibited light output of 85% or more compared to the initial value after driving for 1000 hours, and most of them exhibited light output of 90% or more. Among the samples, the light output of the sample showing a minimum value after driving for 1000 hours was 87.4% compared to the initial value. In contrast, the samples of Comparative Example exhibited the light output of less than 85% compared to the initial value after 1000 hours of driving, and most of them exhibited the light output of 80% or less. Among the samples of Comparative Example, the light output of the sample showing a maximum value after 1000 hours of driving was 81.9% compared to the initial value.

(165) The threshold voltages of the samples of the Inventive Example were also maintained closer to the initial value than the samples of the Comparative Example after driving for 1000 hours. Meanwhile, the turn-on voltages of the samples of the Comparative Example were generally increased after driving for 1000 hours, and the turn-on voltage of Sample 4 was sharply decreased after driving for 1000 hours.

(166) As a result of the driving test of the samples of the Comparative Example and the Inventive Example, it is understood that the samples of the Inventive Example to which the hole pattern is added have the high initial light outputs and well maintain the light outputs even after driving for a long time.

(167) Although some exemplary embodiments have been described herein, it should be understood that the above exemplary embodiments may be variously modified and changed without departing from the spirit and scope of the present disclosure, and the present disclosure includes all of the broad scope of the appended claims.

Claims

1. A UV light emitting diode, comprising: a substrate having a plurality of holes surrounded by a flat surface, wherein at least one of the plurality of holes has a curved bottom surface; a first conductivity type semiconductor layer disposed on the substrate; a second conductivity type semiconductor layer disposed above the first conductivity type semiconductor layer; and an active layer disposed between the first conductivity type semiconductor layer and the second conductivity type semiconductor layer, wherein a distance from the flat surface to the active layer is smaller than a distance from a bottom point or a bottom surface of the plurality of holes to the active layer, and the flat surface is in contact with the first conductivity type semiconductor layer.
2. The UV light emitting diode of claim 1, wherein at least one of the plurality of holes includes an inlet having a diameter of less than 1 μm .
3. The UV light emitting diode of claim 1, wherein a distance between centers of two adjacent holes among the plurality of holes range from 1 μm to 3 μm .
4. The UV light emitting diode of claim 1, wherein: the substrate further includes a light exiting surface disposed opposite to the flat surface and emitting light to an outside of the UV light emitting diode, at least one of the plurality of holes including inclined surfaces, and the inclined surfaces of the at least one of the plurality of holes are disposed between the flat surface of the substrate and the light exiting surface.

5. The UV light emitting diode of claim 1, wherein: the first conductivity type semiconductor layer includes a plurality of cavities therein, and the plurality of cavities corresponds to and is disposed in locations vertically overlapped with regions of the plurality of holes, and wherein a maximum width of each of the plurality of cavities is less than a maximum width of a corresponding hole.
6. The UV light emitting diode of claim 5, wherein: the first conductivity type semiconductor layer includes an AlN layer, and the plurality of cavities is formed in the AlN layer.
7. The UV light emitting diode of claim 1, further comprising: an n-ohmic contact layer disposed in a via hole and contacting the first conductivity type semiconductor layer; a p-ohmic contact layer contacting the second conductivity type semiconductor layer; an n-pad metal layer electrically connected to the n-ohmic contact layer; a p-pad metal layer electrically connected to the p-ohmic contact layer; an n-bump electrically connected to the n-pad metal layer; and a p-bump electrically connected to the p-pad metal layer, wherein the p-pad metal layer is formed so as to surround the n-pad metal layer.
8. The UV light emitting diode of claim 7, wherein the n-bump and the p-bump are disposed in a region over the second conductivity type semiconductor layer.
9. The UV light emitting diode of claim 7, further comprising: a lower insulation layer covering the p-ohmic contact layer and the n-ohmic contact layer, wherein: the lower insulation layer has openings exposing the p-ohmic contact layer and the n-ohmic contact layer, and the n-pad metal layer and the p-pad metal layer are electrically connected to the n-ohmic contact layer and the p-ohmic contact layer through the first openings of the lower insulation layer, respectively.
10. The UV light emitting diode of claim 7, further comprising: an upper insulation layer covering the n-pad metal layer and p-pad metal layer, wherein the upper insulation layer has second openings exposing the n-pad metal layer and the p-pad metal layer, wherein the n-bump and the p-bump are disposed on the upper insulation layer, and electrically connected to the n-pad metal layer and the p-pad metal layer through the second openings of the upper insulation layer.
11. The UV light emitting diode of claim 7, wherein: a peak wavelength of an emission spectrum is 280 nm or less, and after driving at room temperature for 1000 hours, a light output is 85% or more compared to an initial light output.
12. The UV light emitting diode of claim 11, the light output of the UV light emitting diode after driving at room temperature for 1000 hours is greater than or equal to 90% of the initial light output.
13. A UV light emitting diode, comprising: a substrate having a flat surface, the flat surface having a plurality of holes, wherein at least one of the plurality of holes has a curved bottom surface; a first conductivity type semiconductor layer disposed on the substrate and in contact with the flat surface; an active layer disposed on the first conductivity type semiconductor layer; a second conductivity type semiconductor layer disposed on the active layer; an n-ohmic contact layer contacting the first conductivity type semiconductor layer; a p-ohmic contact layer contacting the second conductivity type semiconductor layer; an n-bump electrically connected to the n-ohmic contact layer; and a p-bump electrically connected to the p-ohmic contact layer, wherein the substrate has a hole pattern.
14. The UV light emitting diode of claim 13, wherein: the first conductivity type semiconductor layer includes a plurality of cavities therein, and the first conductivity type semiconductor layer further includes an AlN layer, and the plurality of cavities is formed in the AlN layer.
15. The UV light emitting diode of claim 14, further comprising a plurality of holes, wherein the plurality of cavities is disposed in locations vertically overlapped with regions of the plurality of holes corresponding to the hole pattern, and wherein a maximum width of each of the plurality of cavities is less than a maximum width of a corresponding hole.
16. The UV light emitting diode of claim 15, wherein at least one of the plurality of cavities includes a lower cavity and an upper cavity and at least a portion of the lower cavity is disposed in at least one of the plurality of holes and the upper cavity is disposed above the flat surface.

17. The UV light emitting diode of claim 13, wherein: the second conductivity type semiconductor layer includes a p-type GaN layer, and the p-type GaN layer has a thickness of 50 nm or less, and the p-ohmic contact layer is in-ohmic contact with the p-type GaN layer.
18. The UV light emitting diode of claim 13, further comprising: an upper insulation layer covering the n-ohmic contact layer and the p-ohmic contact layer, wherein the upper insulation layer has openings exposing the n-ohmic contact layer and the p-ohmic contact layer, wherein the n-bump and the p-bump are electrically connected to the n-ohmic contact-layer and the p-ohmic contact layer through the openings of the upper insulation layer, respectively.
19. The UV light emitting diode of claim 18, wherein the upper insulation layer covers side surfaces of the second conductivity type semiconductor layer and the active layer.
20. The UV light emitting diode of claim 18, wherein the openings further comprise: a first opening exposing the n-ohmic contact layer is disposed near one edge of a mesa, and a second opening exposing the p-ohmic contact layer is disposed near an opposite edge of the mesa.
-