



US012404278B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 12,404,278 B2**

(45) **Date of Patent:** **Sep. 2, 2025**

(54) **HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE COMPRISING SAME**

(71) Applicant: **LT MATERIALS CO., LTD.**,
Yongin-si (KR)

(72) Inventors: **Yun-Ji Lee**, Yongin-si (KR); **Min-Ji Park**, Yongin-si (KR); **Won-Jang Jeong**, Yongin-si (KR); **Dong-Jun Kim**, Yongin-si (KR)

(73) Assignee: **LT MATERIALS CO., LTD.**, Yongin (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 910 days.

(21) Appl. No.: **17/608,297**

(22) PCT Filed: **Sep. 25, 2020**

(86) PCT No.: **PCT/KR2020/013036**

§ 371 (c)(1),

(2) Date: **Nov. 2, 2021**

(87) PCT Pub. No.: **WO2021/066397**

PCT Pub. Date: **Apr. 8, 2021**

(65) **Prior Publication Data**

US 2022/0281884 A1 Sep. 8, 2022

(30) **Foreign Application Priority Data**

Oct. 2, 2019 (KR) 10-2019-0122320

(51) **Int. Cl.**

C07D 491/048 (2006.01)

C07D 495/04 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **C07D 491/048** (2013.01); **C07D 495/04** (2013.01); **C07D 519/00** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC **C07D 491/048**; **C07D 495/04**; **C07D 519/00**; **H01L 51/0067**; **H01L 51/0072**;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2013/0292653 A1 11/2013 Park et al.

2016/0141515 A1 5/2016 Hayama et al.

(Continued)

FOREIGN PATENT DOCUMENTS

KR 10-2013-0127567 A 11/2013

KR 10-2016-0002408 A 1/2016

(Continued)

OTHER PUBLICATIONS

Zhang et al., Photoredox-Catalyzed Tandem Insertion/Cyclization Reactions of Difluoromethyl and 1,1-difluoroalkyl Radicals with Biphenyl Isocyanides, Organic Letter, 2015 vol. 17, pp. 4401-4403. (Year: 2015).*

(Continued)


Primary Examiner — Vu A Nguyen

(74) *Attorney, Agent, or Firm* — Birch, Stewart, Kolasch & Birch, LLP

(57) **ABSTRACT**

The present specification relates to a heterocyclic compound represented by Chemical Formula 1, and an organic light emitting device including the same.

14 Claims, 2 Drawing Sheets



(51) **Int. Cl.**

C07D 519/00 (2006.01)
C07F 9/53 (2006.01)
H10K 50/11 (2023.01)
H10K 50/13 (2023.01)
H10K 50/16 (2023.01)
H10K 85/60 (2023.01)
H10K 101/10 (2023.01)
H10K 101/30 (2023.01)
H10K 101/40 (2023.01)

(52) **U.S. Cl.**

CPC *C07F 9/5333* (2013.01); *H10K 85/622*
 (2023.02); *H10K 85/624* (2023.02); *H10K*
85/626 (2023.02); *H10K 85/654* (2023.02);
H10K 85/6572 (2023.02); *H10K 85/6574*
 (2023.02); *H10K 85/6576* (2023.02); *H10K*
50/11 (2023.02); *H10K 50/13* (2023.02); *H10K*
50/16 (2023.02); *H10K 2101/10* (2023.02);
H10K 2101/30 (2023.02); *H10K 2101/40*
 (2023.02)

(58) **Field of Classification Search**

CPC H01L 51/0073; H01L 51/0074; H01L
 51/0056; H01L 51/0058; H01L 51/0054;
C07F 9/5333

See application file for complete search history.

(56)

References Cited

U.S. PATENT DOCUMENTS

2017/0133601 A1 5/2017 Sim et al.
 2017/0133602 A1 5/2017 Lee et al.
 2019/0103560 A1* 4/2019 Jung H05B 33/14
 2020/0308150 A1 10/2020 Lee et al.

FOREIGN PATENT DOCUMENTS

KR 10-2016-0046703 A 4/2016
 KR 10-2018-0076358 A 7/2018
 KR 10-2019-0037925 A 4/2019
 WO WO 2014/199637 A1 12/2014


OTHER PUBLICATIONS

International Search Report for PCT/KR2020/013036 mailed on
 Jan. 21, 2021.


Zhang et al., "Photoredox-Catalyzed Tandem Insertion/Cyclization
 Reactions of Difluoromethyl and 1,1-Difluoroalkyl Radicals with
 Biphenyl Isocyanides", Organic Letters, 2015, vol. 17, pp. 4401-
 4403.

* cited by examiner


【FIG. 1】




【FIG. 2】



【FIG. 3】



【FIG. 4】



【FIG. 5】

CATHODE
ELECTRON INJECTION LAYER
SECOND ELECTRON TRANSFER LAYER
SECOND HOLE BLOCKING LAYER
SECOND STACK LIGHT EMITTING LAYER
SECOND ELECTRON BLOCKING LAYER
SECOND HOLE TRANSFER LAYER
P-TYPE CHARGE GENERATION LAYER
N-TYPE CHARGE GENERATION LAYER
FIRST ELECTRON TRANSFER LAYER
FIRST HOLE BLOCKING LAYER
FIRST STACK LIGHT EMITTING LAYER
FIRST ELECTRON BLOCKING LAYER
FIRST HOLE TRANSFER LAYER
FIRST HOLE INJECTION LAYER
ANODE
SUBSTRATE

1

HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE COMPRISING SAME

TECHNICAL FIELD

The present specification relates to a heterocyclic compound, and an organic light emitting device including the same.

This application claims priority to and the benefits of Korean Patent Application No. 10-2019-0122320, filed with the Korean Intellectual Property Office on Oct. 2, 2019, the entire contents of which are incorporated herein by reference.

BACKGROUND ART

An electroluminescent device is one type of self-emissive display devices, and has an advantage of having a wide viewing angle, and a high response speed as well as having an excellent contrast.

An organic light emitting device has a structure disposing an organic thin film between two electrodes. When a voltage is applied to an organic light emitting device having such a structure, electrons and holes injected from the two electrodes bind and pair in the organic thin film, and light emits as these annihilate. The organic thin film may be formed in a single layer or a multilayer as necessary.

A material of the organic thin film may have a light emitting function as necessary. For example, as a material of the organic thin film, compounds capable of forming a light emitting layer themselves alone may be used, or compounds capable of performing a role of a host or a dopant of a host-dopant-based light emitting layer may also be used. In addition thereto, compounds capable of performing roles of hole injection, hole transfer, electron blocking, hole blocking, electron transfer, electron injection and the like may also be used as a material of the organic thin film.

Development of an organic thin film material has been continuously required for enhancing performance, lifetime or efficiency of an organic light emitting device.

DISCLOSURE

Technical Problem


The present specification is directed to providing a heterocyclic compound, and an organic light emitting device including the same.

Technical Solution

One embodiment of the present specification provides a heterocyclic compound represented by the following Chemical Formula 1.

2

[Chemical Formula 1]



In Chemical Formula 1,

X is O or S,

L is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group,

Z and R1 are each independently a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C2 to C60 alkenyl group; a substituted or unsubstituted C2 to C60 alkynyl group; a substituted or unsubstituted C3 to C60 cycloalkyl group; a substituted or unsubstituted C2 to C60 heterocycloalkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; a substituted or unsubstituted C1 to C20 alkylamine group; a substituted or unsubstituted C6 to C60 arylamine group; a substituted or unsubstituted C2 to C60 heteroarylamine group; or a substituted or unsubstituted phosphine oxide group,

R2 to R5 are each independently hydrogen; deuterium; a halogen group; a cyano group; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C3 to C60 cycloalkyl group; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group,

a is an integer of 1 to 4,

b is an integer of 1 to 3,

m and n are each an integer of 1 to 5, and

when a, b, m and n are each 2 or greater, substituents in the parentheses are the same as or different from each other.

Another embodiment of the present application provides an organic light emitting device including a first electrode; a second electrode provided opposite to the first electrode; and an organic material layer provided between the first electrode and the second electrode, wherein the organic material layer includes the heterocyclic compound represented by Chemical Formula 1.

Another embodiment of the present application provides an organic light emitting device including a first electrode; a first stack provided on the first electrode and including a first light emitting layer; a charge generation layer provided on the first stack; a second stack provided on the charge generation layer and including a second light emitting layer; and a second electrode provided on the second stack, wherein the charge generation layer includes the heterocyclic compound represented by Chemical Formula 1.

Advantageous Effects

A compound described in the present specification can be used as a material of an organic material layer of an organic

3

light emitting device. In the organic light emitting device, the compound is capable of performing a role of a hole injection material, a hole transfer material, a light emitting material, an electron transfer material, an electron injection material or the like. Particularly, the compound can be used as an electron transfer layer material or a charge generation layer material of an organic light emitting device.

Particularly, Chemical Formula 1 has a structure in which dibenzofuran or dibenzothiophene is fused to quinoline, and by having a substituent in the benzene ring of the quinoline, efficiency is improved by properly controlling HOMO and LUMO distributions and thereby allowing charges to migrate smoothly.

Specifically, when using the compound represented by Chemical Formula 1 in an organic material layer, a driving voltage of the device can be lowered, light efficiency can be enhanced, and lifetime properties of the device can be enhanced.

DESCRIPTION OF DRAWINGS

FIG. 1 to FIG. 5 are diagrams each illustrating a lamination structure of an organic light emitting device according to one embodiment of the present specification.

- 100: Substrate
- 200: Anode
- 300: Organic Material Layer
- 301: Hole Injection Layer
- 302: Hole Transfer Layer
- 303: Light Emitting Layer
- 304: Electron Transfer Layer
- 305: Electron Injection Layer
- 306: Charge Generation Layer
- 400: Cathode

MODE FOR DISCLOSURE

Hereinafter, the present specification will be described in more detail.

In the present specification, a certain part “including” certain constituents means capable of further including other constituents, and does not exclude other constituents unless particularly stated on the contrary.

The term “substitution” means a hydrogen atom bonding to a carbon atom of a compound being changed to another substituent, and the position of substitution is not limited as long as it is a position at which the hydrogen atom is substituted, that is, a position at which a substituent can substitute, and when two or more substituents substitute, the two or more substituents may be the same as or different from each other.

In the present specification, “substituted or unsubstituted” means being substituted with one or more substituents selected from the group consisting of a C1 to C60 linear or branched alkyl group; a C2 to C60 linear or branched alkenyl group; a C2 to C60 linear or branched alkynyl group; a C3 to C60 monocyclic or polycyclic cycloalkyl group; a C2 to C60 monocyclic or polycyclic heterocycloalkyl group; a C6 to C60 monocyclic or polycyclic aryl group; a C2 to C60 monocyclic or polycyclic heteroaryl group; a silyl group; a phosphine oxide group; and an amine group, or being unsubstituted, or being substituted with a substituent linking two or more substituents selected from among the substituents illustrated above, or being unsubstituted.

In the present specification, a “case of a substituent being not indicated in a chemical formula or compound structure” means that a hydrogen atom bonds to a carbon atom.

4

However, since deuterium (^2H) is an isotope of hydrogen, some hydrogen atoms may be deuterium.

In one embodiment of the present application, a “case of a substituent being not indicated in a chemical formula or compound structure” may mean that positions that may come as a substituent may all be hydrogen or deuterium. In other words, since deuterium is an isotope of hydrogen, some hydrogen atoms may be deuterium that is an isotope, and herein, a content of the deuterium may be from 0% to 100%.


In one embodiment of the present application, in a “case of a substituent being not indicated in a chemical formula or compound structure”, hydrogen and deuterium may be mixed in compounds when deuterium is not explicitly excluded such as a deuterium content being 0%, a hydrogen content being 100% or substituents being all hydrogen.

In one embodiment of the present application, deuterium is one of isotopes of hydrogen, is an element having deuterium formed with one proton and one neutron as a nucleus, and may be expressed as hydrogen-2, and the elemental symbol may also be written as D or ^2H .


In one embodiment of the present application, an isotope means an atom with the same atomic number (Z) but with a different mass number (A), and may also be interpreted as an element with the same number of protons but with a different number of neutrons.


In one embodiment of the present application, a meaning of a content T % of a specific substituent may be defined as $T2/T1 \times 100 = T\%$ when the total number of substituents that a basic compound may have is defined as T1, and the number of specific substituents among these is defined as T2.

In other words, in one example, having a deuterium content of 20% in a phenyl group represented by



means that the total number of substituents that the phenyl group may have is 5 (T1 in the formula), and the number of deuterium among these is 1 (T2 in the formula). In other words, having a deuterium content of 20% in a phenyl group may be represented by the following structural formulae.





In addition, in one embodiment of the present application, “a phenyl group having a deuterium content of 0%” may mean a phenyl group that does not include a deuterium atom, that is, a phenyl group that has 5 hydrogen atoms.

In the present specification, the halogen may be fluorine, chlorine, bromine or iodine.

In the present specification, the alkyl group includes linear or branched having 1 to 60 carbon atoms, and may be further substituted with other substituents. The number of carbon atoms of the alkyl group may be from 1 to 60, specifically from 1 to 40 and more specifically from 1 to 20. Specific examples thereof may include a methyl group, an ethyl group, a propyl group, an n-propyl group, an isopropyl group, a butyl group, an n-butyl group, an isobutyl group, a tert-butyl group, a sec-butyl group, a 1-methyl-butyl group, a 1-ethylbutyl group, a pentyl group, an n-pentyl group, an isopentyl group, a neopentyl group, a tert-pentyl group, a hexyl group, an n-hexyl group, a 1-methylpentyl group, a 2-methylpentyl group, a 4-methyl-2-pentyl group, a 3,3-dimethylbutyl group, a 2-ethylbutyl group, a heptyl group, an n-heptyl group, a 1-methylhexyl group, a cyclopentylmethyl group, a cyclohexylmethyl group, an octyl group, an n-octyl group, a tert-octyl group, a 1-methylheptyl group, a 2-ethylhexyl group, a 2-propylpentyl group, an n-nonyl group, a 2,2-dimethylheptyl group, a 1-ethyl-propyl group, a 1,1-dimethyl-propyl group, an isohexyl group, a 4-methylhexyl group, a 5-methylhexyl group and the like, but are not limited thereto.

In the present specification, the alkenyl group includes linear or branched having 2 to 60 carbon atoms, and may be further substituted with other substituents. The number of carbon atoms of the alkenyl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 2 to 20. Specific examples thereof may include a vinyl group, a 1-propenyl group, an isopropenyl group, a 1-butenyl group, a 2-butenyl group, a 3-butenyl group, a 1-pentenyl group, a 2-pentenyl group, a 3-pentenyl group, a 3-methyl-1-butenyl group, a 1,3-butadienyl group, an allyl group, a 1-phenylvinyl-1-yl group, a 2-phenylvinyl-1-yl group, a 2,2-diphenylvinyl-1-yl group, a 2-phenyl-2-(naphthyl-1-yl)vinyl-1-yl group, a 2,2-bis(diphenyl-1-yl)vinyl-1-yl group, a stilbenyl group, a styrenyl group and the like, but are not limited thereto.

In the present specification, the alkynyl group includes linear or branched having 2 to 60 carbon atoms, and may be further substituted with other substituents. The number of carbon atoms of the alkynyl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 2 to 20.

In the present specification, the alkoxy group may be linear, branched or cyclic. The number of carbon atoms of the alkoxy group is not particularly limited, but is preferably from 1 to 20. Specific examples thereof may include methoxy, ethoxy, n-propoxy, isopropoxy, i-propyloxy, n-butoxy, isobutoxy, tert-butoxy, sec-butoxy, n-pentyloxy, neopentyloxy, isopentyloxy, n-hexyloxy, 3,3-dimethylbutoxy, 2-ethylbutoxy, n-octyloxy, n-nonyloxy, n-decyloxy, benzoyloxy, p-methylbenzyloxy and the like, but are not limited thereto.

6


In the present specification, the cycloalkyl group includes monocyclic or polycyclic having 3 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the cycloalkyl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be a cycloalkyl group, but may also be different types of cyclic groups such as a heterocycloalkyl group, an aryl group and a heteroaryl group. The number of carbon groups of the cycloalkyl group may be from 3 to 60, specifically from 3 to 40 and more specifically from 5 to 20. Specific examples thereof may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a 3-methylcyclopentyl group, a 2,3-dimethylcyclopentyl group, a cyclohexyl group, a 3-methylcyclohexyl group, a 4-methylcyclohexyl group, a 2,3-dimethylcyclohexyl group, a 3,4,5-trimethylcyclohexyl group, a 4-tert-butylcyclohexyl group, a cycloheptyl group, a cyclooctyl group and the like, but are not limited thereto.

In the present specification, the heterocycloalkyl group includes O, S, Se, N or Si as a heteroatom, includes monocyclic or polycyclic having 2 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the heterocycloalkyl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be a heterocycloalkyl group, but may also be different types of cyclic groups such as a cycloalkyl group, an aryl group and a heteroaryl group. The number of carbon atoms of the heterocycloalkyl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 3 to 20.

In the present specification, the aryl group includes monocyclic or polycyclic having 6 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the aryl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be an aryl group, but may also be different types of cyclic groups such as a cycloalkyl group, a heterocycloalkyl group and a heteroaryl group. The aryl group includes a spiro group. The number of carbon atoms of the aryl group may be from 6 to 60, specifically from 6 to 40 and more specifically from 6 to 25. Specific examples of the aryl group may include a phenyl group, a biphenyl group, a triphenyl group, a naphthyl group, an anthryl group, a chrysenyl group, a phenanthrenyl group, a perylenyl group, a fluoranthenyl group, a triphenylenyl group, a phenalenyl group, a pyrenyl group, a tetracenyl group, a pentacenyl group, a fluorenyl group, an indenyl group, an acenaphthylene group, a benzofluorenyl group, a spirobifluorenyl group, a 2,3-dihydro-1H-indenyl group, a fused ring thereof, and the like, but are not limited thereto.


In the present specification, the fluorenyl group may be substituted, and adjacent substituents may bond to each other to form a ring.

When the fluorenyl group is substituted,



7

-continued



and the like may be included, however, the structure is not limited thereto.

In the present specification, the heteroaryl group includes S, O, Se, N or Si as a heteroatom, includes monocyclic or polycyclic having 2 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the heteroaryl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be a heteroaryl group, but may also be different types of cyclic groups such as a cycloalkyl group, a heterocycloalkyl group and an aryl group. The number of carbon atoms of the heteroaryl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 3 to 25. Specific examples of the heteroaryl group may include a pyridyl group, a pyrrolyl group, a pyrimidyl group, a pyridazinyl group, a furanyl group, a thiophene group, an imidazolyl group, a pyrazolyl group, an oxazolyl group, an isoxazolyl group, a thiazolyl group, an isothiazolyl group, a triazolyl group, a furazanyl group, an oxadiazolyl group, a thiadiazolyl group, a dithiazolyl group, a tetrazolyl group, a pyranlyl group, a thiopyranlyl group, a diazinyl group, an oxazinyl group, a thiazinyl group, a dioxynyl group, a triazinyl group, a tetrazinyl group, a quinolyl group, an isoquinolyl group, a quinazoliny group, an isoquinazoliny group, a quinoxaliny group, a naphthyridyl group, an acridinyl group, a phenanthridinyl group, an imidazopyridinyl group, a diazanaphthalenyl group, a triazaindene group, an indolyl group, an indoliziny group, a benzothiazolyl group, a benzoxazolyl group, a benzimidazolyl group, a benzothiophene group, a benzofuran group, a dibenzothiophene group, a dibenzofuran group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenazinyl group, a dibenzosilole group, spirobi(dibenzosilole), a dihydrophenazinyl group, a phenoxazinyl group, a phenanthridyl

8

group, an imidazopyridinyl group, a thienyl group, an indolo[2,3-a]carbazolyl group, an indolo[2,3-b]carbazolyl group, an indoliny group, a 10,11-dihydro-dibenzo[b,f]azepine group, a 9,10-dihydroacridinyl group, a phenanthrazinyl group, a phenothiazinyl group, a phthalazinyl group, a naphthylidiny group, a phenanthrolinyl group, a benzo[c][1,2,5]thiadiazolyl group, a 5,10-dihydrobenzo[b,e][1,4]azasilinyl group, a pyrazolo[1,5-c]quinazoliny group, a pyrido[1,2-b]indazolyl group, a pyrido[1,2-a]imidazo[1,2-e]indoliny group, a 5,11-dihydroindeno[1,2-b]carbazolyl group and the like, but are not limited thereto.

In the present specification, the silyl group is a substituent including Si, having the Si atom directly linked as a radical, and is represented by $\text{—Si(R101)(R102)(R103)}$. R101 to R103 are the same as or different from each other, and may be each independently a substituent formed with at least one of hydrogen; deuterium; a halogen group; an alkyl group; an alkenyl group; an alkoxy group; a cycloalkyl group; a heterocycloalkyl group; an aryl group; and a heteroaryl group. Specific examples of the silyl group may include a trimethylsilyl group, a triethylsilyl group, a t-butyl dimethylsilyl group, a vinyl dimethylsilyl group, a propyl dimethylsilyl group, a triphenylsilyl group, a diphenylsilyl group, a phenylsilyl group and the like, but are not limited thereto.

In the present specification, the phosphine oxide group is represented by $\text{—P(=O)(R104)(R105)}$, and R104 and R105 are the same as or different from each other and may be each independently a substituent formed with at least one of hydrogen; deuterium; a halogen group; an alkyl group; an alkenyl group; an alkoxy group; a cycloalkyl group; a heterocycloalkyl group; an aryl group; and a heteroaryl group. The phosphine oxide group may specifically be substituted with an aryl group, and as the aryl group, the examples described above may be applied. Examples of the phosphine oxide group may include a diphenylphosphine oxide group, a dinaphthylphosphine oxide group and the like, but are not limited thereto.

In the present specification, the amine group is represented by —N(R106)(R107) , and R106 and R107 are the same as or different from each other and may be each independently a substituent formed with at least one of hydrogen; deuterium; a halogen group; an alkyl group; an alkenyl group; an alkoxy group; a cycloalkyl group; a heterocycloalkyl group; an aryl group; and a heteroaryl group. The amine group may be selected from the group consisting of —NH_2 ; a monoalkylamine group; a monoarylamine group; a monoheteroarylamine group; a dialkylamine group; a diarylamine group; a diheteroarylamine group; an alkylarylamine group; an alkylheteroarylamine group; and an arylheteroarylamine group, and although not particularly limited thereto, the number of carbon atoms is preferably from 1 to 30. Specific examples of the amine group may include a methylamine group, a dimethylamine group, an ethylamine group, a diethylamine group, a phenylamine group, a naphthylamine group, a biphenylamine group, a dibiphenylamine group, an anthracenylamine group, a 9-methyl-anthracenylamine group, a diphenylamine group, a phenyl naphthylamine group, a ditolylamine group, a phenyltolylamine group, a triphenylamine group, a biphenyl naphthylamine group, a phenylbiphenylamine group, a biphenylfluorenylamine group, a phenyltriphenylamine group, a biphenyltriphenylamine group and the like, but are not limited thereto.

In the present specification, descriptions on the aryl group provided above may be applied to the arylene group except that the arylene group is not a monovalent group.

In the present specification, descriptions on the heteroaryl group provided above may be applied to the heteroarylene group except that the heteroarylene group is not a monovalent group.

In the present specification, an “adjacent” group may mean a substituent substituting an atom directly linked to an atom substituted by the corresponding substituent, a substituent sterically most closely positioned to the corresponding substituent, or another substituent substituting an atom substituted by the corresponding substituent. For example, two substituents substituting ortho positions in a benzene ring, and two substituents substituting the same carbon in an aliphatic ring may be interpreted as groups “adjacent” to each other.

As the aliphatic or aromatic hydrocarbon ring or heteroring that the adjacent groups may form, the structures illustrated as the cycloalkyl group, the heterocycloalkyl group, the aryl group and the heteroaryl group described above may be applied except for those that are not a monovalent group.

One embodiment of the present specification provides a heterocyclic compound represented by Chemical Formula 1.

Particularly, Chemical Formula 1 has a structure in which dibenzofuran or dibenzothiophene is fused to quinoline, and by having a substituent in the benzene ring of the quinoline, HOMO and LUMO tend to have a decreased overlap, and light emission efficiency is improved. In addition, through properly controlling an energy level, a migration barrier of charges is lowered, which improves device efficiency. In addition, by attaching a substituent having HT properties, particularly an aryl group, to R1 of the ring including N of the quinoline, the shape of the molecule may be improved, and thermal stability of the molecule may increase there-through.

In one embodiment of the present specification, X is O or S.

In one embodiment of the present specification, X is O.

In another embodiment, X is S.

In one embodiment of the present specification, L is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group.

In one embodiment of the present specification, L is a direct bond; a substituted or unsubstituted C6 to C30 arylene group; or a substituted or unsubstituted C2 to C30 heteroarylene group.

In one embodiment of the present specification, L is a direct bond; or a substituted or unsubstituted C6 to C30 arylene group.

In one embodiment of the present specification, L is a direct bond; a substituted or unsubstituted phenylene group; a substituted or unsubstituted biphenylene group; a substituted or unsubstituted terphenylene group; a substituted or unsubstituted naphthylene group; a substituted or unsubstituted anthracenylene group; a substituted or unsubstituted triphenylenylene group; or a substituted or unsubstituted phenanthrenylene group.

In one embodiment of the present specification, L is a direct bond; a phenylene group; a biphenylene group; a terphenylene group; a naphthylene group; an anthracenylene group; a triphenylenylene group; or a phenanthrenylene group.

In one embodiment of the present specification, L is a direct bond; or a phenylene group.

In one embodiment of the present specification, Z is a substituted or unsubstituted C1 to C60 alkyl group; a sub-

stituted or unsubstituted C2 to C60 alkenyl group; a substituted or unsubstituted C2 to C60 alkynyl group; a substituted or unsubstituted C3 to C60 cycloalkyl group; a substituted or unsubstituted C2 to C60 heterocycloalkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; a substituted or unsubstituted C1 to C20 alkylamine group; a substituted or unsubstituted C6 to C60 arylamine group; a substituted or unsubstituted C2 to C60 heteroarylamine group; or a substituted or unsubstituted phosphine oxide group.

In one embodiment of the present specification, Z is a substituted or unsubstituted C1 to C30 alkyl group; a substituted or unsubstituted C2 to C30 alkenyl group; a substituted or unsubstituted C2 to C30 alkynyl group; a substituted or unsubstituted C3 to C30 cycloalkyl group; a substituted or unsubstituted C2 to C30 heterocycloalkyl group; a substituted or unsubstituted C6 to C30 aryl group; a substituted or unsubstituted C2 to C30 heteroaryl group; a substituted or unsubstituted C1 to C10 alkylamine group; a substituted or unsubstituted C6 to C30 arylamine group; a substituted or unsubstituted C2 to C30 heteroarylamine group; or a substituted or unsubstituted phosphine oxide group.

In one embodiment of the present specification, Z is a substituted or unsubstituted C6 to C30 aryl group; a substituted or unsubstituted C2 to C30 heteroaryl group; or a substituted or unsubstituted phosphine oxide group.

In one embodiment of the present specification, Z is a substituted or unsubstituted phenyl group; a biphenyl group; a terphenyl group; a naphthyl group; a triphenylenyl group; a phenanthrenyl group; an anthracenyl group; a dimethylfluorenyl group; a diphenylfluorenyl group; a spirobifluorenyl group; an isoquinolinyl group; a quinazolinyl group; a phenoxazinyl group; a phenothiazinyl group; an indolocarbazole group; a benzonaphthothiophene group; a substituted or unsubstituted pyrazole group; a substituted or unsubstituted pyridine group; a substituted or unsubstituted pyrimidine group; a substituted or unsubstituted triazine group; a substituted or unsubstituted carbazole group; a substituted or unsubstituted phenanthrolinyl group; a substituted or unsubstituted dibenzofuran group; a substituted or unsubstituted dibenzothiophene group; a substituted or unsubstituted dihydroacridine group; or a substituted or unsubstituted phosphine oxide group.

In one embodiment of the present specification, Z is a phenyl group unsubstituted or substituted with a cyano group, a phenyl group or a carbazole group; a biphenyl group; a terphenyl group; a naphthyl group; a triphenylenyl group; a phenanthrenyl group; an anthracenyl group; a dimethylfluorenyl group; a diphenylfluorenyl group; a spirobifluorenyl group; an isoquinolinyl group; a quinazolinyl group; a phenoxazinyl group; a phenothiazinyl group; an indolocarbazole group; a benzonaphthothiophene group; a pyrazole group unsubstituted or substituted with a phenyl group; a pyridine group unsubstituted or substituted with a phenyl group or a pyridine group; a pyrimidine group unsubstituted or substituted with a phenyl group or a biphenyl group; a triazine group unsubstituted or substituted with one or more substituents selected from the group consisting of a phenyl group unsubstituted or substituted with a naphthyl group or a cyano group, a biphenyl group, a naphthyl group, a dimethylfluorenyl group, a dibenzofuran group, a

11

dibenzothiophene group and a carbazole group unsubstituted or substituted with a phenyl group; a carbazole group unsubstituted or substituted with a phenyl group; a phenanthroline group unsubstituted or substituted with a phenyl group; a dibenzofuran group unsubstituted or substituted with a phenyl group or a naphthyl group; a dibenzothiophene group unsubstituted or substituted with a phenyl group or a naphthyl group; a dihydroacridine group unsubstituted or substituted with a methyl group or a phenyl group; or a phosphine oxide group unsubstituted or substituted with a phenyl group.

In one embodiment of the present specification, R1 is a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C2 to C60 alkenyl group; a substituted or unsubstituted C2 to C60 alkynyl group; a substituted or unsubstituted C3 to C60 cycloalkyl group; a substituted or unsubstituted C2 to C60 heterocycloalkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; a substituted or unsubstituted C1 to C20 alkylamine group; a substituted or unsubstituted C6 to C60 arylamine group; a substituted or unsubstituted C2 to C60 heteroarylamine group; or a substituted or unsubstituted phosphine oxide group.

In one embodiment of the present specification, R1 is a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C3 to C60 cycloalkyl group; a substituted or unsubstituted C2 to C60 heterocycloalkyl group; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.

In one embodiment of the present specification, R1 is a C6 to C60 substituted or unsubstituted aryl group; or a C2 to C60 substituted or unsubstituted heteroaryl group.

In one embodiment of the present specification, R1 is a C6 to C30 substituted or unsubstituted aryl group; or a C2 to C30 substituted or unsubstituted heteroaryl group.

In one embodiment of the present specification, R1 is a C6 to C30 substituted or unsubstituted aryl group.

In one embodiment of the present specification, R1 is a substituted or unsubstituted phenyl group; a substituted or unsubstituted naphthyl group; a substituted or unsubstituted anthracenyl group; a substituted or unsubstituted phenanthrenyl group; a substituted or unsubstituted pyrenyl group; or a substituted or unsubstituted perylene group.

In one embodiment of the present specification, R1 is a phenyl group unsubstituted or substituted with a naphthyl group; a naphthyl group; an anthracenyl group; a phenanthrenyl group; a pyrenyl group; or a perylene group.

In one embodiment of the present specification, R2 to R5 are each independently hydrogen; deuterium; a halogen group; a cyano group; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C3 to C60 cycloalkyl group; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.

In one embodiment of the present specification, R2 to R5 are each independently hydrogen; deuterium; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.

In one embodiment of the present specification, R2 to R5 are each independently hydrogen; or deuterium.

12


In one embodiment of the present specification, R2 to R5 are hydrogen.

In one embodiment of the present specification, m may be 1 or 2.


In one embodiment of the present specification, n may be an integer of 1 to 3.

In the heterocyclic compound provided in one embodiment of the present specification, Chemical Formula 1 is represented by the following Chemical Formula 2 or 3.

[Chemical Formula 2]



[Chemical Formula 3]




In Chemical Formulae 2 and 3,

L, Z, R1, R4, R5, a, b, m and n have the same definitions as in Chemical Formula 1.


In the heterocyclic compound provided in one embodiment of the present specification, Chemical Formula 1 is represented by any one of the following Chemical Formulae 4 to 6.

[Chemical Formula 4]




13

-continued

**14**





-continued

[Chemical Formula 6]




In Chemical Formulae 4 to 6,
X, L, Z, R1 to R5, a, b, m and n have the same definitions
as in Chemical Formula 1.

In one embodiment of the present specification, Chemical
Formula 1 may be represented by any one of the following
compounds, but is not limited thereto.




15



-continued


5

16




6


7




8



9



10





17

-continued


11

18


12






13



14




19




-continued

15


20



17



19




16

18

20


21



-continued


21

22




22


23



24




23



-continued


25

24




26


27




28




29



30




25



-continued


31

26




32

33




34


35



36




27




-continued

28


37



38




39



40

29




30

-continued



41

42




43


44



31


-continued
45

32




46


47




48




49



50




33




-continued

51

34




52





53


54



55


56



35


-continued

57


36

58


59




60




61



62




37




-continued

63


38



64




65



66


39



-continued


67

40




68


69




70




71



72




41



-continued


73

42




74


75




76




77



78




43



-continued


79

44




80


81




82




83



84




45



-continued


85

46




86


87




88




89



90




47



-continued


91

48




92


93



94




49



-continued


95

50




96


97



98




51



-continued


99

52




100

101



102




53


-continued

54


103




104




105




106



55


-continued

107


56

108


109



110




57



-continued


111

58




112


113



114




59




-continued
115

60




116


117



118




61




-continued

119


62



120



121



122



63

-continued

64



123

124





125

126





66




129

130




67




-continued

131


68



132




133




134

69




-continued
135

70







136

137




138






139

72



141



140

142


143

73

74


-continued

144





145

146






147

148




75



76


-continued

149




150

151




152

153



154


77




-continued

155


78




156




157






158



159



160

79**80**

-continued

161

164

5

10

15

20

162

25

30

35

40

45



163

50

55


60

65




165


166



-continued




168




65

-continued

169




170






45

171





83

-continued


**84**

-continued



85

-continued



177

5

10


15

20

25

86

-continued



179


30

35

40

45

180



178



50

55

60



65

181



87

-continued

**88**

-continued

182

5

10

15

20

25

30

35

40

183


45

50

55


60

65




184

185






186



89

-continued

**90**

-continued

187

190

5

10

15

20

188

25

30

35

40

189

45



50

55

60



65

191



91

-continued

**92**

-continued

192

5

10

15

20

25

30

35

193 40


45

50

55

60


65









194

195




196





95

-continued

**96**

-continued

203

206

5

10

15

20

25

204

30

35

40

45

205

50




55

60

65


207

208



97

-continued



209


5

10

15

20

25




210

30

35

40

45



211


55

60


65

98


-continued



212






213



214

99

-continued

**100**

-continued

215

5

10

15

216 20

25

30

35

40

217

45


50

55


60

65




218



219



-continued



-continued

223

5

10

15

20

25

221

30

35

40

45




222

50

55


60

65



103

-continued



226

5

10

15

20

25

30

35

40

227


45

50


55

60

65


**104**

-continued





228

229



105

-continued

**106**

-continued

230

5

10

15

20

25

30

35

40

231


45

50


55

60


65



232






233



234

107

-continued

**108**

-continued

235

5

10

15

20

25

236

30

35

40

45

237



50

55

60

65


238



239

109

-continued

**110**

-continued

240

242

5

10

15

20

25

243


30

35

40

45

241




50

244

55




60

65



111

-continued

**112**

-continued

245

5

10

15

20

246

25

30

35

40

247

45



50

55

60

65


248






249

113

-continued



**114**

-continued



115

-continued

**116**

-continued

254

5

10

15

20

25

30

35

40

255


45

50

55

60


65



256




257

258



117

-continued

**118**

-continued

259

262

5

10

15

20

260

263

25

30

35

40

261

45




264

50

55


60

65



119

-continued


**120**

-continued

265


268

5
10
15
20
266
25
30
35
40




269

45
267
50
55
60
65



121


-continued

**122**

-continued

270

272




30

35

40

271

273




65

45

50


55

60



123

-continued



274

275

5

10

15

20

25

30

35

40

276 45

50


55

60

65

124

-continued






277

278

279

125

-continued

**126**

-continued

280

283

5

10

15

20

281

25

284

30

35

40

282 45




50

285

55




60

65



127

-continued

**128**

-continued


286

5

10

15

20



289

25


287

30

35

40

45



290


288

50

55

60




65



291


129

-continued

**130**


-continued

292



295


293



296

45

294



297

50


55

60

65

131

-continued




298

5

10

15

20



299


25

30

35

40

45



300

50


55

60


65

132


-continued



301




302



303

133


-continued




304

134


-continued




307




308




309




305



306



55




310


65

135


-continued




311



312




313




314

136


-continued




315



316




317



318

137

-continued

**138**


-continued

5

10


15

20





321

322







323

324



139




140

-continued


325

326




327

328




329

330




331

332




141




-continued
333


142




334




335




336




337



338




339




340

143


-continued
341

144




342


343




344




345




346




347




348




349



350




145




-continued
351


146




352




353



354




355




356

147




-continued
357


148




358




359



360



361



362



149

150

-continued



363

364




365

366



367




151

152



-continued

368





369

370




371

372




153



-continued


373

154




374


375




376




377



378




155




-continued

379


156




380




381



382




383




384

157


-continued
385

158




386


387




388



389



390






159

-continued


391

160


392




393



394




395



396


161



-continued


397

162




398


399




400




401



402




163



-continued


403

164




404


405




406




407



408




165



-continued


409

166




410


411




412




413




414



167


-continued

415


168

416


417




418




419



420




169




-continued

421

170




422





423

424




425

426




171




-continued

427


172




428




429



430




431



432


173



-continued


433

174




434


435




436




437



438




175



-continued


439

176




440


441




442




443



444




177



-continued


445

178




446


447




448




449



450




179



-continued


451

180




452


453




454






455



456




181




-continued

457


182



459



461






458

460

462

183




184

-continued


463

464




465




466



467


468




185

-continued

469

186


471



470


472

473



474


187



-continued


475

188




476


477




478




479



480




189




481


190



482




483



484

191




192

-continued



485

486





487

488




489

490




193



-continued


491

194




492


493



494




195




196


-continued
495



496




497




498

197


-continued
499

198




500


501




502




503




504




199

-continued
505


200



506




507




508

201




-continued
509

202




510


511




512



203


-continued
513

204




514


515




516




517



518




205

-continued
519



206

520





521

522




523


524




207

-continued
525


208



526




527




528


209

-continued
529


210



530




531



532


211




-continued

533


212




534




535



536




537




538

213




-continued
539


214



540




541



542


215




-continued

543


216



544



545




546

217


-continued

547




218


548







549




550




220




221

-continued
555


222



556




557




558

223


-continued
559

224




560


561




562




563



564




225




-continued
565

226




566


567



568



227




228

-continued



569

570




571

572



229




230

-continued



573

574




575

576




231



-continued


577

232




578


579




580




581



582




233



-continued


583

234




584


585




586



587



588




235


236

-continued

589





590






591


592




237




238

-continued
593

595



597



594

596

598




239

240

-continued


599

600




601


602




241

-continued
603


242




604




605



606




607



608


243




-continued

609


244



610




611




612


245

-continued
613


246



614




615




616

247




-continued
617

248




618

619



620





249

250



-continued
621

622





623

624




625

626




251



-continued


627

252




628


629




630




631



632




253




-continued

633


254



634




635



636


255



-continued


637

256




638


639




640




641



642




257




-continued

643


258




644




645



646



647



648



259

260

-continued



649

650





651

652




653

654




261




-continued

655


262



656



657




658

263


-continued

264





659

660



661

662





265

266

-continued



663

664





665

666




667

668




267



-continued


669

268




670


671



672




269




-continued
673

270




674


675




676




677




678



271


-continued
679

272




680


681




682




683



684




273




-continued
685


274



686




687




688

275




-continued
689

276




690


691



692




277




-continued

693


278



694



695




696

279


-continued

697





280

698





699

700



701

702





281

282

-continued



703

704





705

706



707

708





283

284

-continued



709

710





711

712





713

714





715

716





717

718



719

720





287

288

-continued



721

722





723

724





725

726




727

728




289



-continued


729

290




730


731




732




733



734




291




-continued
735


292




736




737



738




739



740


293




-continued

741


294




742




743



744



745



746



295

296

-continued



747

748





749

750



751


752



297


-continued

753





298

754



755


756



299


-continued

757





300

758





759

760



761


762



301


-continued

763





302

764





765

766




767

768




303



-continued


769

304




770


771




772




773



774



305




306

-continued



775

776






777

778




307




-continued

779

308




781



780


782

783




784


309

-continued
785


310



786



787



788



311

312

-continued



789

790





791

792



793

794





313

314

-continued



795

796





797

798



799


800



315


-continued

801





316

802





803

804




805

806




317



-continued


807

318




808


809




810




811



812




319


-continued
813

320


814




815




816



817



818





321

322

-continued



819

820





821

822



823


824



323


-continued

825





324

826





827

828




829


830





326




833



832



834



835

In addition, by introducing various substituents to the structure of Chemical Formula 1, compounds having unique properties of the introduced substituents may be synthesized. For example, by introducing substituents normally used as hole injection layer materials, hole transfer layer materials, light emitting layer materials, electron transfer layer materials and charge generation layer materials used for manufacturing an organic light emitting device to the core structure, materials satisfying conditions required for each organic material layer may be synthesized. In addition, the energy band gap may be finely controlled, and with a high T1 value obtained therefrom, an organic light emitting device with superior efficiency may be provided. Herein, the T1 value means an energy level value in a triplet state.

In addition, by introducing various substituents with different properties to the structure of Chemical Formula 1, efficiency may increase through controlling HOMO and LUMO, and interfacial properties may be improved through controlling the molecular weight.

One embodiment of the present specification provides an organic light emitting device including a first electrode; a second electrode; and an organic material layer provided between the first electrode and the second electrode, wherein the organic material layer includes the heterocyclic compound represented by Chemical Formula 1.

In one embodiment of the present specification, the first electrode may be an anode, and the second electrode may be a cathode.

In another embodiment of the present specification, the first electrode may be a cathode, and the second electrode may be an anode.

In one embodiment of the present specification, the organic light emitting device may be a blue organic light emitting device, and the heterocyclic compound according to Chemical Formula 1 may be used as a material of the blue organic light emitting device. For example, the heterocyclic compound according to Chemical Formula 1 may be included in a charge generation layer or an electron transfer layer of the blue organic light emitting device.

In another embodiment of the present specification, the organic light emitting device may be a green organic light emitting device, and the heterocyclic compound according to Chemical Formula 1 may be used as a material of the green organic light emitting device. For example, the heterocyclic compound according to Chemical Formula 1 may be included in a charge generation layer or an electron transfer layer of the green organic light emitting device.

In another embodiment of the present specification, the organic light emitting device may be a red organic light emitting device, and the heterocyclic compound according to Chemical Formula 1 may be used as a material of the red organic light emitting device. For example, the heterocyclic compound according to Chemical Formula 1 may be included in a charge generation layer or an electron transfer layer of the red organic light emitting device.

Specific descriptions on the heterocyclic compound represented by Chemical Formula 1 are the same as the descriptions provided above.

The organic light emitting device of the present specification may be manufactured using common organic light emitting device manufacturing methods and materials except that one or more of the organic material layers are formed using the heterocyclic compound described above.

The heterocyclic compound may be formed into an organic material layer through a solution coating method as well as a vacuum deposition method when manufacturing the organic light emitting device. Herein, the solution coat-

ing method means spin coating, dip coating, inkjet printing, screen printing, a spray method, roll coating and the like, but is not limited thereto.

The organic material layer of the organic light emitting device of the present specification may be formed in a single layer structure, but may be formed in a multilayer structure in which two or more organic material layers are laminated. For example, the organic light emitting device of the present disclosure may have a structure including a hole injection layer, a hole transfer layer, a light emitting layer, an electron transfer layer, an electron injection layer and the like as the organic material layer. However, the structure of the organic light emitting device is not limited thereto, and may include a smaller number of organic material layers.

In the organic light emitting device of the present specification, the organic material layer includes a charge generation layer, and the charge generation layer may include the heterocyclic compound of Chemical Formula 1. When including the heterocyclic compound in the charge generation layer, the band gap may be readily controlled facilitating carrier migration, and thermal properties may be improved by increasing the molecular weight.

In the organic light emitting device of the present specification, the organic material layer includes an electron transfer layer, and the electron transfer layer may include the heterocyclic compound of Chemical Formula 1. When using the heterocyclic compound as an electron transfer material, HOMO and LUMO may be controlled depending on the substituent position, and electron transfer efficiency is superior. In addition, a higher T1 is obtained compared to existing electron transfer materials leading to a low light emitter loss, and by preventing electrons from migrating in a reverse direction, excellent device efficiency is obtained.

The organic light emitting device of the present disclosure may further include one, two or more layers selected from the group consisting of a light emitting layer, a hole injection layer, a hole transfer layer, an electron injection layer, an electron transfer layer, an electron blocking layer and a hole blocking layer.

FIG. 1 to FIG. 5 illustrate a lamination order of electrodes and organic material layers of an organic light emitting device according to one embodiment of the present specification. However, the scope of the present application is not limited to these diagrams, and structures of organic light emitting devices known in the art may also be used in the present application.

FIG. 1 illustrates an organic light emitting device in which an anode (200), an organic material layer (300) and a cathode (400) are consecutively laminated on a substrate (100). However, the structure is not limited to such a structure, and as illustrated in FIG. 2, an organic light emitting device in which a cathode, an organic material layer and an anode are consecutively laminated on a substrate may also be obtained.

FIG. 3 and FIG. 4 illustrate cases of the organic material layer being a multilayer. The organic light emitting device according to FIG. 3 includes a hole injection layer (301), a hole transfer layer (302), a light emitting layer (303), an electron transfer layer (304) and a charge generation layer (306), and the organic light emitting device according to FIG. 4 includes a hole injection layer (301), a hole transfer layer (302), a light emitting layer (303), an electron transfer layer (304) and an electron injection layer (305). However, the scope of the present application is not limited to such a lamination structure, and as necessary, layers other than the light emitting layer may not be included, and other necessary functional layers may be further added.

329

The organic material layer including the heterocyclic compound represented by Chemical Formula 1 may further include other materials as necessary.

The organic light emitting device according to one embodiment of the present specification includes a first electrode; a first stack provided on the first electrode and including a first light emitting layer; a charge generation layer provided on the first stack; a second stack provided on the charge generation layer and including a second light emitting layer; and a second electrode provided on the second stack, wherein the charge generation layer may include the heterocyclic compound represented by Chemical Formula 1.

The organic light emitting device according to one embodiment of the present specification includes a first electrode; a second electrode; and an organic material layer provided between the first electrode and the second electrode, wherein the organic material layer includes two or more stacks, and the two or more stacks each independently include a light emitting layer, a charge generation layer is included between the two or more stacks, and the charge generation layer may include the heterocyclic compound represented by Chemical Formula 1.

The organic light emitting device according to one embodiment of the present specification includes a first electrode; a second electrode; and an organic material layer provided between the first electrode and the second electrode, wherein the organic material layer includes a first stack including a first light emitting layer; a charge generation layer provided on the first stack; and a second stack including a second light emitting layer, and the charge generation layer may include the heterocyclic compound represented by Chemical Formula 1.

In addition, the organic light emitting device according to one embodiment of the present specification includes an anode, a cathode, and two or more stacks provided between the anode and the cathode, the two or more stacks each independently include a light emitting layer, a charge generation layer is included between the two or more stacks, and the charge generation layer includes the heterocyclic compound represented by Chemical Formula 1.

In addition, the organic light emitting device according to one embodiment of the present specification includes an anode, a first stack provided on the anode and including a first light emitting layer, a charge generation layer provided on the first stack, a second stack provided on the charge generation layer and including a second light emitting layer, and a cathode provided on the second stack. Herein, the charge generation layer may include the heterocyclic compound represented by Chemical Formula 1. When the heterocyclic compound is included in the charge generation layer and used, superior efficiency is obtained as a charge generation layer material due to an electron-friendly substituent structure and a fused structure of quinoline-dibenzofuran or quinoline-dibenzothiophene friendly for hole migration.

Specifically, in the charge generation layer, controlling an energy level is important for an electron transfer layer and a hole transfer layer to favorably receive electrons and holes, respectively. By properly mixing a moiety with ET properties and a moiety with HT properties, the compound of the

330

present disclosure is capable of controlling an energy level through properly controlling a substituent to have a deep LUMO level or a shallow HOMO level, and high efficiency as a charge generation layer may be obtained therethrough.

In addition, the first stack and the second stack may each independently further include one or more types of the hole injection layer, the hole transfer layer, the hole blocking layer, the electron transfer layer, the electron injection layer and the like described above.

The charge generation layer includes an N-type charge generation layer, and the N-type charge generation layer includes the heterocyclic compound represented by Chemical Formula 1 and, in addition to the compound, may further include a dopant known in the art.

As the organic light emitting device according to one embodiment of the present specification, an organic light emitting device having a 2-stack tandem structure is illustrated in FIG. 5.

Herein, the first electron blocking layer, the first hole blocking layer, the second hole blocking layer and the like described in FIG. 5 may not be included in some cases.

In the organic light emitting device according to one embodiment of the present specification, materials other than the heterocyclic compound represented by Chemical Formula 1 are illustrated below, however, these are for illustrative purposes only and not for limiting the scope of the present application, and may be replaced by materials known in the art.

As the anode material, materials having relatively large work function may be used, and transparent conductive oxides, metals, conductive polymers or the like may be used. Specific examples of the anode material include metals such as vanadium, chromium, copper, zinc and gold, or alloys thereof; metal oxides such as zinc oxide, indium oxide, indium tin oxide (ITO) and indium zinc oxide (IZO); combinations of metals and oxides such as ZnO:Al or SnO₂:Sb; conductive polymers such as poly(3-methylthiophene), poly[3,4-(ethylene-1,2-dioxy)thiophene](PEDOT), polypyrrole and polyaniline, and the like, but are not limited thereto.

As the cathode material, materials having relatively small work function may be used, and metals, metal oxides, conductive polymers or the like may be used. Specific examples of the cathode material include metals such as magnesium, calcium, sodium, potassium, titanium, indium, yttrium, lithium, gadolinium, aluminum, silver, tin and lead, or alloys thereof; multilayer structure materials such as LiF/Al or LiO₂/Al, and the like, but are not limited thereto.

As the hole injection material, known hole injection materials may be used, and for example, phthalocyanine compounds such as copper phthalocyanine disclosed in U.S. Pat. No. 4,356,429, or starburst-type amine derivatives such as tris(4-carbazoyl-9-ylphenyl)amine (TCTA), 4,4',4''-tri[phenyl(m-tolyl)amino]triphenylamine (m-MTDATA) or 1,3,5-tris[4-(3-methylphenylphenylamino)phenyl]benzene (m-MTDAPB) described in the literature [Advanced Material, 6, p. 677 (1994)], polyaniline/dodecylbenzene sulfonic acid, poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate), polyaniline/camphor sulfonic acid or polyaniline/poly(4-styrenesulfonate) that are conductive polymers having solubility, and the like, may be used.

331

As the hole transfer material, pyrazoline derivatives, arylamine-based derivatives, stilbene derivatives, triphenyl-diamine derivatives and the like may be used, and low molecular or high molecular materials may also be used.

As the electron transfer material, metal complexes of oxadiazole derivatives, anthraquinodimethane and derivatives thereof, benzoquinone and derivatives thereof, naphthoquinone and derivatives thereof, anthraquinone and derivatives thereof, tetracyanoanthraquinodimethane and derivatives thereof, fluorenone derivatives, diphenyldicyanoethylene and derivatives thereof, diphenoquinone derivatives, 8-hydroxyquinoline and derivatives thereof, and the like, may be used in addition to the heterocyclic compound, and high molecular materials may also be used as well as low molecular materials.

As examples of the electron injection material, LiF is typically used in the art, however, the present application is not limited thereto.

As the light emitting material, red, green or blue light emitting materials may be used, and as necessary, two or more light emitting materials may be mixed and used. Herein, two or more light emitting materials may be used by being deposited as individual sources of supply or by being premixed and deposited as one source of supply. In addition, fluorescent materials may also be used as the light emitting material, however, phosphorescent materials may also be used. As the light emitting material, materials emitting light

332

by bonding electrons and holes injected from an anode and a cathode, respectively, may be used alone, however, materials having a host material and a dopant material involving in light emission together may also be used.



When mixing light emitting material hosts, same series hosts may be mixed, or different series hosts may be mixed. For example, any two or more types of materials among n-type host materials or p-type host materials may be selected and used as a host material of a light emitting layer.

The organic light emitting device according to one embodiment of the present specification may be a top-emission type, a bottom-emission type or a dual-emission type depending on the materials used.

The heterocyclic compound according to one embodiment of the present specification may also be used in an organic electronic device including an organic solar cell, an organic photo conductor, an organic transistor and the like under a similar principle used in the organic light emitting device.

Hereinafter, the present specification will be described in more detail with reference to examples, however, these are for illustrative purposes only, and the scope of the present application is not limited thereto.


<Preparation Example 1> Preparation of Compound 1



333

334

-continued



55

1) Preparation of Compound 1-3

After dissolving dibenzo[b,d]furan-1-ylboronic acid (30 g, 0.14 mol, 1 eq.) and 2,6-dibromoaniline (52.5 g, 0.21 mol, 1.5 eq.) in 1,4-dioxane (300 ml) and H₂O (90 ml), Pd(PPh₃)₄ (8 g, 0.007 mol, 0.05 eq.) and K₃PO₄ (89 g, 0.42 mol, 3 eq.) were introduced thereto, and the result was stirred for 4 hours under reflux.

The reaction solution was concentrated, then dissolved by introducing methylene chloride (MC) thereto, and then extracted with water, and the organic layer was dried with anhydrous Na₂SO₄. The solution was concentrated and

dissolved again in methylene chloride, and after adsorbing the result to silica gel (250 ml), an MC/hexane column was performed to obtain Compound 1-3 (36 g).

2) Preparation of Compound 1-2

After dissolving Compound 1-3 (36 g, 0.11 mol, 1 eq.) and benzaldehyde (17.5 g, 0.17 mol, 1.5 eq.) in 1,2-dichlorobenzene (360 ml) and trifluoromethanesulfonic acid (20 ml), the result was stirred for 3 hours under reflux.

335

NaHCO₃ dissolved in H₂O was introduced to the reaction solution for neutralization. The solution was concentrated and dissolved in a small amount of MC, and then MC/methanol (MeOH) slurried and filtered. Compound 1-2 (28 g) was obtained in a 60% yield.

3) Preparation of Compound 1-1

After dissolving Compound 1-2 (28 g, 0.066 mol, 1 eq.) and bis(pinacolato)diboron (25 g, 0.099 mol, 1.5 eq.) in 1,4-dioxane (300 ml), Pd(dppf)Cl₂ (2.4 g, 0.033 mol, 0.05 eq.) and KOAc (19 g, 0.198 mol, 3 eq.) were introduced thereto, and the result was stirred for 4 hours under reflux. After the reaction was completed, the result was extracted with MC and water, and then the organic layer was dried with anhydrous MgSO₄ and then silica gel filtered. The result was precipitated with MC/MeOH and the precipitates were filtered to obtain Intermediate 1-1 (25 g) in a 81% yield.

336





4) Preparation of Compound 1

After dissolving Compound 1-1 (11 g, 0.0235 mol, 1 eq.) and 2-([1,1'-biphenyl]-4-yl)-4-(4-bromonaphthalen-1-yl)-6-phenyl-1,3,5-triazine (12.8 g, 0.025 mol, 1.05 eq.) in 1,4-dioxane (100 ml) and H₂O (30 ml), Pd(PPh₃)₄ (1.4 g, 0.00118 mol, 0.05 eq.) and K₃PO₄ (15 g, 0.71 mol, 3 eq.) were introduced thereto, and the result was stirred for 4 hours under reflux.

The reaction solution was cooled, then MeOH slurried to precipitate solids, and filtered. The solids were dissolved in 1,2-dichlorobenzene and silica gel filtered. The organic solution was concentrated, MC/MeOH slurried, and then filtered to obtain Compound 1 (12 g) in a 67% yield.

Compound P was synthesized in the same manner as in Preparation Example 1 except that Intermediate A of the following Table 1 was used instead of 2-([1,1'-biphenyl]-4-yl)-4-(4-bromonaphthalen-1-yl)-6-phenyl-1,3,5-triazine.







TABLE 1

Compound Number	Intermediate A	Compound P	Yield
1			67%
4			78%

337

338







TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
7			72%
8			79%
15			79%

339

340





TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
18			85%
21			82%
32			91%

341

342





TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
35			78%
38			82%

343

344







TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
41			78%
44			81%

345

346







TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
47			92%
50			88%
53			89%

347

348

TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
58			78%
61			82%
63			95%

349

350

TABLE 1-continued













Compound Number	Intermediate A	Compound P	Yield
67			92%
73			90%
76			89%

TABLE 1-continued

93%







TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
86			88%
90			81%
92			92%

355

356

TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
95			89%
101			90%
103			92%

357

358

TABLE 1-continued












Compound Number	Intermediate A	Compound P	Yield
107			95%
110			87%

TABLE 1-continued

Compound Number	Intermediate A	Compound P	Yield
113			86%
115			82%


361

<Preparation Example 2> Preparation of Compound 122



362

-continued



1) Preparation of Compound 122-4

Compound 122-4 (38 g, 92% yield) was obtained in the same manner as in Preparation Example 1 except that 2-bromo-5-chloroaniline was used instead of 2,6-dibromoaniline. 2) Preparation of Compound 122-3

After dissolving Compound 122-4 (38 g, 0.129 mol, 1 eq.) in tetrahydrofuran (THF), triethylamine (TEA) (0.516 mol) and benzoyl chloride (0.194 mol) were added thereto at 0° C., and then the result was stirred for 1 hour at room temperature. After the reaction was finished, the result was extracted with distilled water and ethyl acetate (EA). The organic layer was dried with MgSO₄, then filtered, and concentrated. The result was adsorbed to silica gel, and purified by column chromatography using dichloromethane and hexane as a developing solvent to obtain Compound 122-3 (48.5 g) in a 95% yield.

3) Preparation of Compound 122-2

After dissolving Compound 122-3 (48.5 g, 0.121 mol, 1 eq.) in nitrobenzene, POCl₃ (0.182 mol) was added thereto, and the result was stirred for 17 hours at 150° C. After the reaction was finished, the result was neutralized at room temperature, and then extracted with distilled water and dichloromethane. The organic layer was dried with MgSO₄, then filtered, and concentrated. The concentrated residue was slurried with MeOH, and then filtered to obtain Compound 122-2 (26 g) in a 56% yield.

363

4) Preparation of Compound 122-1

After adding 4,4,4',4',5,5,5',5'-octamethyl-2,2'-bi(1,3,2-dioxaborolane) (0.102 mol), Pd(dba)₂ (0.0068 mol), XPhos (0.0136 mol), KoAc (0.204 mol) and 1,4-dioxane to Compound 122-2 (26 g, 0.068 mol, 1 eq.), the result was stirred for 5 hours at 110° C. After the reaction was completed, the result was base filtered, and then washed with dichloromethane. The organic solution was concentrated, and then dissolved in a small amount of chloroform, and passed through silica gel. The solution was concentrated, and then MC/MeOH slurried to obtain Compound 122-1 (31 g) in a 97% yield.

5) Preparation of Compound 122

After dissolving Compound 122-1 (10 g, 0.039 mol, 1 eq.) and 2-chloro-4,6-diphenyl-1,3,5-triazine (0.041 mol, 1.05





364

eq.) in 1,4-dioxane (100 ml) and H₂O (30 ml), Pd(PPh₃)₄ (0.0019 mol, 0.05 eq.) and K₃PO₄ (0.117 mol, 3 eq.) were introduced thereto, and the result was stirred for 4 hours under reflux.

The reaction solution was cooled, then MeOH slurried to precipitate solids, and then filtered. The solids were dissolved in 1,2-dichlorobenzene and silica gel filtered. The organic solution was concentrated, MC/MeOH slurried, and then filtered to obtain Compound 122 (20 g) in a 78% yield.

Compound P was synthesized in the same manner as in Preparation Example 2 except that Intermediate A of the following Table 2 was used instead of 2-([1,1'-biphenyl]-4-yl)-4-chloro-6-phenyl-1,3,5-triazine.







TABLE 2

Compound Number	Intermediate A	Compound P	Yield
122			78%
124			78%

365

366







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
126			72%
130			79%
135			79%

367

368







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
138			69%
147			82%
149			84%

369

370





TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
152			78%
155			82%
161			82%

371

372







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
164			81%
168			92%

373

374







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
172			93%
178			95%
181			96%

375

376







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
186			87%
190			83%
194			75%

377

378







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
198			84%
202			79%
206			80%

379

380

TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
210			86%
214			88%
218			89%

381

382

TABLE 2-continued











Compound Number	Intermediate A	Compound P	Yield
222			91%
226			82%
230			83%





TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
234			93%
238			94%

385

386





TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
242			89%
246			78%

387

388







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
250			79%
254			75%

389

390







TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
258			81%
262			82%
266			91%

391

392

TABLE 2-continued

Compound Number	Intermediate A	Compound P	Yield
270			92%
274			86%
278			87%

Compound P was obtained in the same manner as in Preparation Example 2 except that 2-bromo-4-chloroaniline instead of 2-bromo-5-chloroaniline, and Intermediate A of the following Table 3 was used instead of 2-([1,1'-biphenyl]-4-yl)-4-chloro-6-phenyl-1,3,5-triazine.

TABLE 3











Compound Number	Intermediate A	Compound P	Yield
282			82%
286			81%
290			92%

TABLE 3-continued

Compound Number	Intermediate A	Compound P	Yield
294			78%
298			93%

397

398

TABLE 3-continued



















Compound Number	Intermediate A	Compound P	Yield
302			72%
306			79%
310			79%
314			69%

TABLE 3-continued

Compound Number	Intermediate A	Compound P	Yield
318			82%
326			84%
330			78%
334			82%
338			81%

401

402

TABLE 3-continued









Compound Number	Intermediate A	Compound P	Yield
342			82%
346			92%
350			93%
358			88%

TABLE 3-continued







Compound Number	Intermediate A	Compound P	Yield
366			91%
370			92%
374			87%

TABLE 3-continued







Compound Number	Intermediate A	Compound P	Yield
378			75%
382			79%
386			81%

TABLE 3-continued











Compound Number	Intermediate A	Compound P	Yield
390			92%
394			88%
398			78%







TABLE 3-continued

Compound Number	Intermediate A	Compound P	Yield
402			79%
406			82%

411

412

TABLE 3-continued

Compound Number	Intermediate A	Compound P	Yield
410			86%
414			89%
418			92%

413

414







TABLE 3-continued

Compound Number	Intermediate A	Compound P	Yield
422	<chem>Clc1nc(C2=CC=C3C(=C2)S=C3C4=CC=CC=C4)cc(C5=CC=CC=C5)n1</chem>	<chem>c1ccc(cc1)-c2nc(C3=CC=C4C(=C3)S=C4C5=CC=CC=C5)cc(C6=CC=CC=C6)n2-c7ccc8c(c7)c9ccccc9n8</chem>	93%
426	<chem>Clc1nc(C2=CC=C3C(=C2)OC3C4=CC=CC=C4)cc(C5=CC=CC=C5)n1</chem>	<chem>c1ccc(cc1)-c2nc(C3=CC=C4C(=C3)OC4C5=CC=CC=C5)cc(C6=CC=CC=C6)n2-c7ccc8c(c7)c9ccccc9n8</chem>	83%

415

416

TABLE 3-continued

Compound Number	Intermediate A	Compound P	Yield
430			78%
434			72%
438			81%

Compound P was synthesized in the same manner as in Preparation Example 1 except that dibenzo[b,d]thiophen-1-ylboronic acid, and Intermediate A of the following Table 4 was used instead of 2-([1,1'-biphenyl]-4-yl)-4-(4-bromonaphthalen-1-yl)-6-phenyl-1,3,5-triazine.

417

418

TABLE 4







Compound Number	Intermediate A	Compound P	Yield
442			81%
446			78%
450			75%

TABLE 4-continued

[illegible]

421

422

TABLE 4-continued







Compound Number	Intermediate A	Compound P	Yield
466			79%
470			79%
474			69%

TABLE 4-continued







Compound Number	Intermediate A	Compound P	Yield
478			82%
482			84%
486			82%

TABLE 4-continued







Compound Number	Intermediate A	Compound P	Yield
490			78%
498			82%
502			75%

TABLE 4-continued









Compound Number	Intermediate A	Compound P	Yield
506			82%
510			72%

TABLE 4-continued

Compound Number	Intermediate A	Compound P	Yield
514			81%
518			83%

431

432

TABLE 4-continued







Compound Number	Intermediate A	Compound P	Yield
522			82%
526			78%
530			72%

TABLE 4-continued







Compound Number	Intermediate A	Compound P	Yield
534			81%
538			85%
542			91%

TABLE 4-continued









Compound Number	Intermediate A	Compound P	Yield
546			88%
550			84%

TABLE 4-continued

Compound Number	Intermediate A	Compound P	Yield
554			92%
558			87%







Compound P was synthesized in the same manner as in Preparation Example 2 except that 5-chloro-2-(dibenzo[b,d]thiophen-1-yl)aniline was obtained instead of Compound 122-4 using

dibenzo[b,d]thiophen-1-ylboronic acid instead of dibenzo[b,d]furan-1-ylboronic acid, and Intermediate B of the following Table 5 was used instead of 2-chloro-4,6-diphenyl-1,3,5-triazine.

439

440

TABLE 5

Compound Number	Intermediate B	Compound P	Yield
562			82%
566			81%
570			78%

441

442

TABLE 5-continued







Compound Number	Intermediate B	Compound P	Yield
574			78%
578			72%
582			71%

TABLE 5-continued







Compound Number	Intermediate B	Compound P	Yield
586			79%
590			79%
594			69%

TABLE 5-continued

78%

447

448

TABLE 5-continued







Compound Number	Intermediate B	Compound P	Yield
610			82%
614			71%
618			82%

TABLE 5-continued















Compound Number	Intermediate B	Compound P	Yield
622			72%
626			68%
630			91%







TABLE 5-continued

Compound Number	Intermediate B	Compound P	Yield
634			72%
638			75%
642			89%
646			69%

453

454







TABLE 5-continued

Compound Number	Intermediate B	Compound P	Yield
650			75%
654			78%
658			81%

455

456







TABLE 5-continued

Compound Number	Intermediate B	Compound P	Yield
662			91%
666			89%
670			82%

457

458







TABLE 5-continued

Compound Number	Intermediate B	Compound P	Yield
674			81%
678			78%
682			77%

459

460



TABLE 5-continued

Compound Number	Intermediate B	Compound P	Yield
686			82%
690			91%
694			68%

461

462

TABLE 5-continued

Compound Number	Intermediate B	Compound P	Yield
698			71%

Compound P was obtained in the same manner as in Preparation Example 2 except that 4-chloro-2-(dibenzo[b,d]thiophen-1-yl) aniline was synthesized using dibenzo[b,d]thiophen-1-ylboronic acid instead of dibenzo [b,d]furan-1-

ylboronic acid and 2-bromo-4-chloroaniline instead of 2-bromo-5-chloroaniline, and Intermediate A of the following Table 6 was used instead of 2-chloro-4,6-diphenyl-1,3,5-triazine.

TABLE 6





Compound Number	Intermediate A	Compound P	Yield
702			81%
706			72%

TABLE 6-continued









Compound Number	Intermediate A	Compound P	Yield
710			78%
714			72%
718			86%
722			79%

TABLE 6-continued









Compound Number	Intermediate A	Compound P	Yield
726			79%
730			69%
734			82%
742			78%

TABLE 6-continued













Compound Number	Intermediate A	Compound P	Yield
750			69%
754			82%
758			82%

TABLE 6-continued

Compound Number	Intermediate A	Compound P	Yield
762			68%
766			71%
770			72%

471

472

TABLE 6-continued







Compound Number	Intermediate A	Compound P	Yield
774			82%
778			89%
782			82%

TABLE 6-continued







Compound Number	Intermediate A	Compound P	Yield
786			89%
790			82%
794			83%

TABLE 6-continued







Compound Number	Intermediate A	Compound P	Yield
798			78%
802			79%
806			69%

TABLE 6-continued













Compound Number	Intermediate A	Compound P	Yield
810		 v	71%
814			77%
818			82%

TABLE 6-continued

Compound Number	Intermediate A	Compound P	Yield
822			85%
826			69%
830			67%

481

Compounds were prepared in the same manner as in the preparation examples, and the synthesis identification results are shown in the following Table 7.

TABLE 7

Compound	FD-MS
1	m/z = 778.90 (C56H34N4O = 778.27)
4	m/z = 571.66 (C43H25NO = 571.19)
8	m/z = 521.61 (C39H23NO = 521.18)
12	m/z = 597.70 (C45H27NO = 597.21)
15	m/z = 628.76 (C46H32N2O = 628.25)
18	m/z = 599.68 (C43H25N3O = 599.20)
21	m/z = 725.83 (C53H31N3O = 725.25)
25	m/z = 736.86 (C55H32N2O = 736.25)
28	m/z = 702.80 (C51H30N2O2 = 702.23)
32	m/z = 676.76 (C48H28N4O = 676.23)
35	m/z = 652.74 (C46H28N4O = 652.23)
38	m/z = 742.82 (C52H30N4O2 = 742.24)
41	m/z = 742.82 (C52H30N4O2 = 742.24)
44	m/z = 732.85 (C50H28N4OS = 732.20)
47	m/z = 768.90 (C55H36N4O = 768.29)
50	m/z = 728.84 (C52H32N4O = 728.2)
53	m/z = 867.99 (C62H37N5O = 867.30)
58	m/z = 884.05 (C63H37N3OS = 883.27)
61	m/z = 697.76 (C49H32NO2P = 697.22)
63	m/z = 597.70 (C45H27NO = 597.21)
67	m/z = 785.93 (C60H35NO = 785.27)
73	m/z = 651.75 (C47H29N3O = 651.23)
76	m/z = 665.74 (C47H27N3O2 = 665.21)
78	m/z = 741.83 (C53H31N3O2 = 741.24)
81	m/z = 665.74 (C47H27N3O2 = 665.21)
83	m/z = 681.80 (C47H27N3OS = 681.19)
86	m/z = 816.94 (C59H36N4O = 816.29)
90	m/z = 664.75 (C47H28N4O = 664.23)
92	m/z = 727.85 (C53H33N3O = 727.26)
95	m/z = 575.66 (C41H25N3O = 575.20)
101	m/z = 651.75 (C47H29N3O = 651.23)
103	m/z = 803.94 (C59H37N3O = 803.29)
107	m/z = 665.74 (C47H27N3O2 = 665.21)
110	m/z = 681.80 (C47H27N3OS = 681.19)
113	m/z = 741.83 (C53H31N3O2 = 741.24)
115	m/z = 816.94 (C59H36N4O = 816.29)
122	m/z = 576.64 (C40H24N4O = 576.20)
124	m/z = 728.84 (C52H32N4O = 728.26)
126	m/z = 652.74 (C46H28N4O = 652.23)
130	m/z = 666.72 (C46H26N4O2 = 666.21)
135	m/z = 742.82 (C52H30N4O2 = 742.24)
138	m/z = 817.93 (C58H35N5O = 817.28)
142	m/z = 692.80 (C49H32N4O = 692.26)
144	m/z = 804.93 (C58H36N4O = 804.29)
147	m/z = 521.61 (C39H23NO = 521.18)
149	m/z = 571.66 (C43H25NO = 571.19)
152	m/z = 649.78 (C49H31NO = 649.24)
155	m/z = 548.63 (C40H24N2O = 548.19)
161	m/z = 573.68 (C43H27NO = 573.21)
164	m/z = 603.73 (C43H25NOS = 603.17)
168	m/z = 752.90 (C56H36N2O = 752.28)
172	m/z = 652.74 (C46H28N4O = 652.23)
174	m/z = 634.72 (C47H26N2O = 634.20)
178	m/z = 751.87 (C55H33N3O = 751.26)
181	m/z = 758.89 (C52H30N4OS = 758.21)
186	m/z = 742.82 (C52H30N4O2 = 742.24)
190	m/z = 742.82 (C52H30N4O2 = 742.24)
194	m/z = 732.85 (C50H28N4OS = 732.20)
198	m/z = 690.75 (C47H26N6O = 690.22)
201	m/z = 618.74 (C43H26N2OS = 618.18)
202	m/z = 660.76 (C49H28N2O = 660.22)
206	m/z = 741.83 (C53H31N3O2 = 741.24)
210	m/z = 712.83 (C53H32N2 = 712.25)
214	m/z = 649.78 (C49H31NO = 649.24)
218	m/z = 727.85 (C53H33N3O = 727.26)
221	m/z = 665.74 (C47H27N3O2 = 665.21)
222	m/z = 665.74 (C47H27N3O2 = 665.21)
226	m/z = 741.83 (C53H31N3O2 = 741.24)
230	m/z = 816.94 (C59H36N4O = 816.29)
234	m/z = 740.85 (C53H32N4O = 740.26)
238	m/z = 651.75 (C47H29N3O = 651.23)
241	m/z = 727.85 (C53H33N3O = 727.26)
242	m/z = 727.85 (C53H33N3O = 727.26)

482

TABLE 7-continued

Compound	FD-MS
246	m/z = 665.74 (C47H27N3O2 = 665.21)
250	m/z = 741.83 (C53H31N3O2 = 741.24)
254	m/z = 816.94 (C59H36N4O = 816.29)
258	m/z = 740.85 (C53H32N4O = 740.26)
261	m/z = 651.75 (C47H29N3O = 651.23)
262	m/z = 665.74 (C47H27N3O2 = 665.21)
266	m/z = 681.80 (C47H27N3OS = 681.19)
270	m/z = 791.89 (C57H33N3O2 = 791.26)
274	m/z = 816.94 (C59H36N4O = 816.29)
278	m/z = 691.82 (C50H33N3O = 691.26)
280	m/z = 652.74 (C46H28N4O = 652.23)
282	m/z = 728.84 (C52H32N4O = 728.26)
286	m/z = 728.84 (C52H32N4O = 728.26)
290	m/z = 666.72 (C46H26N4O2 = 666.21)
294	m/z = 742.82 (C52H30N4O2 = 742.24)
298	m/z = 741.84 (C52H31N5O = 741.25)
301	m/z = 778.90 (C56H34N4O = 778.27)
302	m/z = 728.84 (C52H32N4O = 728.26)
306	m/z = 741.84 (C52H31N5O = 741.25)
310	m/z = 521.61 (C39H23NO = 521.18)
314	m/z = 597.70 (C45H27NO = 597.21)
318	m/z = 548.63 (C40H24N2O = 548.19)
321	m/z = 527.63 (C37H21NOS = 527.13)
322	m/z = 552.66 (C40H28N2O = 552.22)
326	m/z = 663.76 (C49H29NO2 = 663.22)
330	m/z = 662.78 (C49H30N2O = 662.24)
334	m/z = 652.74 (C46H28N4O = 652.23)
338	m/z = 549.62 (C39H23N3O = 549.18)
341	m/z = 571.66 (C43H25NO = 571.19)
342	m/z = 521.61 (C39H23NO = 521.18)
346	m/z = 597.70 (C45H27NO = 597.21)
350	m/z = 548.63 (C40H24N2O = 548.19)
354	m/z = 676.80 (C50H32N2O = 676.25)
358	m/z = 751.87 (C55H33N3O = 751.26)
361	m/z = 602.68 (C43H26N2O2 = 602.20)
362	m/z = 742.88 (C53H30N2OS = 742.21)
366	m/z = 728.84 (C52H32N4O = 728.26)
370	m/z = 742.82 (C52H30N4O2 = 742.24)
374	m/z = 742.82 (C52H30N4O2 = 742.24)
378	m/z = 867.99 (C62H37N5O = 867.30)
381	m/z = 628.76 (C46H32N2O = 628.25)
382	m/z = 602.68 (C43H26N2O2 = 602.20)
386	m/z = 675.77 (C49H29N3O = 675.23)
390	m/z = 713.82 (C53H31NO2 = 713.24)
394	m/z = 662.78 (C49H30N2O = 662.24)
398	m/z = 649.78 (C49H31NO = 649.24)
401	m/z = 727.85 (C53H33N3O = 727.26)
402	m/z = 727.85 (C53H33N3O = 727.26)
406	m/z = 665.74 (C47H27N3O2 = 665.21)
410	m/z = 741.83 (C53H31N3O2 = 741.24)
414	m/z = 816.94 (C59H36N4O = 816.29)
418	m/z = 664.75 (C47H28N4O = 664.23)
421	m/z = 803.94 (C59H37N3O = 803.29)
422	m/z = 681.80 (C47H27N3OS = 681.19)
426	m/z = 665.74 (C47H27N3O2 = 665.21)
430	m/z = 741.83 (C53H31N3O2 = 741.24)
434	m/z = 757.90 (C53H31N3OS = 757.22)
438	m/z = 664.75 (C47H28N4O = 664.23)
441	m/z = 744.90 (C52H32N4S = 744.23)
442	m/z = 682.79 (C46H26N4OS = 682.18)
446	m/z = 682.79 (C46H26N4OS = 682.18)
450	m/z = 757.90 (C52H31NS = 757.23)
454	m/z = 784.97 (C55H36N4S = 784.27)
458	m/z = 758.89 (C52H30N4OS = 758.21)
461	m/z = 587.73 (C43H25NS = 587.17)
462	m/z = 537.67 (C39H23NS = 537.16)
466	m/z = 613.77 (C45H27NS = 613.19)
470	m/z = 564.70 (C40H24N2S = 564.17)
474	m/z = 602.74 (C43H26N2S = 602.18)
478	m/z = 675.84 (C50H29NS = 675.20)
480	m/z = 644.82 (C46H32N2S = 644.23)
481	m/z = 543.70 (C37H21NS2 = 543.11)
482	m/z = 543.70 (C37H21NS2 = 543.11)
486	m/z = 758.89 (C52H30N4OS = 758.21)
490	m/z = 615.74 (C43H25N3S = 615.18)
494	m/z = 845.02 (C60H36N4S = 844.27)
498	m/z = 758.89 (C52H30N4OS = 758.21)
501	m/z = 758.89 (C52H30N4OS = 758.21)

483

TABLE 7-continued

Compound	FD-MS
502	m/z = 884.06 (C62H37N5S = 883.28)
506	m/z = 821.00 (C58H36N4S = 820.27)
510	m/z = 744.90 (C52H32N4S = 744.23)
514	m/z = 774.95 (C52H30N4S2 = 774.19)
518	m/z = 850.06 (C59H35N3S2 = 849.23)
521	m/z = 697.87 (C47H27N3S2 = 697.16)
522	m/z = 756.91 (C53H32N4S = 756.23)
526	m/z = 743.91 (C53H33N3S = 743.24)
530	m/z = 743.91 (C53H33N3S = 743.24)
534	m/z = 833.01 (C59H36N4S = 832.27)
538	m/z = 681.80 (C47H27N3OS = 681.19)
541	m/z = 870.07 (C63H39N3S = 869.29)
542	m/z = 591.72 (C41H25N3S = 591.18)
546	m/z = 757.90 (C53H31N3OS = 757.22)
550	m/z = 757.90 (C53H31N3OS = 757.22)
554	m/z = 668.81 (C46H28N4S = 668.20)
558	m/z = 773.96 (C53H31N3S2 = 773.20)
561	m/z = 682.79 (C46H26N4OS = 682.18)
562	m/z = 682.79 (C46H26N4OS = 682.18)
566	m/z = 758.89 (C52H30N4OS = 758.21)
570	m/z = 774.95 (C52H30N4S2 = 774.19)
574	m/z = 681.81 (C46H27N5S = 681.20)
578	m/z = 587.73 (C43H25NS = 587.17)
581	m/z = 589.75 (C43H27NS = 589.19)
582	m/z = 543.70 (C37H21NS2 = 543.11)
586	m/z = 668.81 (C46H28N4S = 668.20)
590	m/z = 834.98 (C58H34N4OS = 834.25)
594	m/z = 564.70 (C40H24N2S = 564.17)
598	m/z = 602.74 (C43H26N2S = 602.18)
601	m/z = 568.73 (C40H28N2S = 568.20)
602	m/z = 644.82 (C46H32N2S = 644.23)
606	m/z = 675.84 (C50H29NS = 675.20)
610	m/z = 869.04 (C62H36N4S = 868.27)
614	m/z = 884.06 (C62H37N5S = 883.28)
618	m/z = 834.00 (C58H35N5S = 833.26)
621	m/z = 744.90 (C52H32N4S = 744.23)
622	m/z = 821.00 (C58H36N4S = 820.27)
626	m/z = 758.89 (C52H30N4OS = 758.21)
630	m/z = 901.11 (C62H36N4S2 = 900.24)
634	m/z = 758.89 (C52H30N4OS = 758.21)
638	m/z = 678.84 (C49H30N2S = 678.21)
641	m/z = 644.82 (C46H32N2S = 644.23)
642	m/z = 618.74 (C43H26N2OS = 618.18)
646	m/z = 691.84 (C49H29N3S = 691.21)
650	m/z = 613.77 (C45H27NS = 613.19)
654	m/z = 697.87 (C47H27N3S2 = 697.16)
658	m/z = 773.96 (C53H31N3S2 = 773.20)
661	m/z = 591.72 (C41H25N3S = 591.18)
662	m/z = 667.82 (C47H29N3S = 667.21)
666	m/z = 743.91 (C53H33N3S = 743.24)
670	m/z = 681.80 (C47H27N3OS = 681.19)
674	m/z = 681.80 (C47H27N3OS = 681.19)
678	m/z = 756.91 (C53H32N4S = 756.23)
681	m/z = 820.01 (C59H37N3S = 819.27)

484

TABLE 7-continued

Compound	FD-MS
682	m/z = 667.82 (C47H29N3S = 667.21)
686	m/z = 681.80 (C47H27N3OS = 681.19)
670	m/z = 757.90 (C53H31N3OS = 757.22)
674	m/z = 743.91 (C53H33N3S = 743.24)
678	m/z = 783.98 (C56H37N3S = 783.27)
681	m/z = 820.01 (C59H37N3S = 819.27)
682	m/z = 667.82 (C47H29N3S = 667.21)
686	m/z = 681.80 (C47H27N3OS = 681.19)
690	m/z = 757.90 (C53H31N3OS = 757.22)
694	m/z = 743.91 (C53H33N3S = 743.24)
698	m/z = 783.98 (C56H37N3S = 783.27)
701	m/z = 592.71 (C40H24N4S = 592.17)
702	m/z = 668.81 (C46H28N4S = 668.20)
706	m/z = 682.79 (C46H26N4OS = 682.18)
710	m/z = 758.89 (C52H30N4OS = 758.21)
714	m/z = 834.00 (C58H35N5S = 833.26)
718	m/z = 681.81 (C46H27N5S = 681.20)
721	m/z = 613.77 (C45H27NS = 613.19)
722	m/z = 665.84 (C49H31NS = 665.22)
726	m/z = 539.65 (C37H21N3S = 539.15)
730	m/z = 564.70 (C40H24N2S = 564.17)
734	m/z = 678.84 (C49H30N2S = 678.21)
738	m/z = 692.87 (C50H32N2S = 692.23)
741	m/z = 676.83 (C49H28N2S = 676.20)
742	m/z = 768.92 (C54H32N4S = 768.23)
746	m/z = 758.89 (C52H30N4OS = 758.21)
750	m/z = 748.91 (C50H28N4S2 = 748.18)
754	m/z = 758.89 (C52H30N4OS = 758.21)
758	m/z = 834.00 (C58H35N5S = 833.26)
761	m/z = 706.81 (C47H26N6S = 706.19)
762	m/z = 644.82 (C46H32N2S = 644.23)
766	m/z = 757.90 (C53H31N3OS = 757.22)
770	m/z = 678.84 (C49H30N2S = 678.21)
774	m/z = 619.80 (C43H25NS2 = 619.14)
778	m/z = 678.84 (C49H30N2S = 678.21)
781	m/z = 591.72 (C41H25N3S = 591.18)
782	m/z = 667.82 (C47H29N3S = 667.21)
786	m/z = 820.01 (C59H37N3S = 819.27)
790	m/z = 681.80 (C47H27N3OS = 681.19)
794	m/z = 757.90 (C53H31N3OS = 757.22)
798	m/z = 833.01 (C59H36N4S = 832.27)
801	m/z = 667.82 (C47H29N3S = 667.21)
802	m/z = 667.82 (C47H29N3S = 667.21)
806	m/z = 681.80 (C47H27N3OS = 681.19)
810	m/z = 668.81 (C46H28N4S = 668.20)
814	m/z = 743.91 (C53H33N3S = 743.24)
818	m/z = 743.91 (C53H33N3S = 743.24)
821	m/z = 757.90 (C53H31N3OS = 757.22)
823	m/z = 833.01 (C59H36N4S = 832.27)
826	m/z = 707.88 (C50H33N3S = 707.24)
828	m/z = 757.90 (C53H31N3OS = 757.22)
830	m/z = 783.98 (C56H37N3S = 783.27)
831	m/z = 756.91 (C53H32N4S = 756.23)

TABLE 8

NO	¹ H NMR (CDCl ₃ , 300 Mz)
1	δ = 8.55(t, 2H), 8.30~8.21(m, 5H), 8.02~8.01(m, 3H), 7.85~7.90(m, 4H), 7.66(m, 2H), 7.54~7.25(m, 18H)
4	δ = 9.15(s, 1H), 8.93(t, 2H), 8.30~8.02(m, 8H), 7.92~7.82(m, 6H), 7.66(m, 2H), 7.54~7.32(m, 6H)
8	δ = 8.93(m, 2H), 8.30(m, 2H), 8.21(m, 1H), 8.12(m, 2H), 8.02(t, 1H), 7.93~7.82(m, 7H), 7.66(m, 2H), 7.54~7.32(m, 6H)
12	δ = 8.93(t, 2H), 8.30(t, 2H), 8.21(d, 2H), 8.12(t, 2H), 8.02(d, 1H), 7.92~7.82(m, 7H), 7.66(m, 2H), 7.54~7.25(m, 10H)
15	δ = 8.30(t, 2H), 8.21(d, 1H), 8.02(d, 1H), 7.92~7.89(m, 2H), 7.66(m, 2H), 7.54~7.32(m, 8H), 7.05~7.02(m, 4H), 6.73~6.69(m, 4H), 6.55(m, 2H), 1.72(s, 2H)
18	δ = 8.88(m, 1H), 8.30(m, 4H), 8.10~8.06(m, 4H), 7.89~7.92(m, 2H), 7.81(m, 1H), 7.69~7.66(m, 2H), 7.54~7.32(m, 11H)
21	δ = 8.55(m, 3H), 8.30(m, 4H), 8.21(d, 1H), 8.10~8.02(m, 5H), 7.92~7.89(m, 2H), 7.81(m, 1H), 7.66(m, 2H), 7.55~7.32(m, 13H)
25	δ = 9.66(d, 1H), 8.93(t, 2H), 8.55(t, 2H), 8.21~8.12(m, 5H), 7.89~7.79(m, 9H), 7.68~7.51(m, 8H), 7.38~7.29(m, 5H)

TABLE 8-continued

NO	¹ H NMR (CDCl ₃ , 300 Mz)
28	δ = 8.33(d, 1H), 8.21(d, 1H), 8.02(m, 1H), 7.91~7.89(m, 6H), 7.66(m, 2H), 7.54~7.50(m, 3H), 7.39~7.32(m, 6H), 6.92~6.89(m, 4H), 6.79~6.69(m, 4H), 6.59(m, 2H)
32	δ = 8.49(t, 2H), 8.30(t, 2H), 8.21(d, 1H), 8.02~7.89(m, 9H), 7.66~7.32(m, 12H)
35	δ = 8.30~8.21(m, 8H), 8.02(d, 1H), 7.92~7.89(m, 2H), 7.66~7.32(m, 17H)
38	δ = 8.30~8.21(m, 6H), 8.02(d, 1H), 7.92~7.81(m, 5H), 7.70~7.32(m, 18H)
41	δ = 8.30(m, 2H), 8.21(d, 1H), 8.02(d, 1H), 7.92~7.85(m, 5H), 7.75(m, 1H), 7.66~7.32(m, 20H)
44	δ = 9.09(d, 1H), 8.49~8.45(t, 2H), 8.30(t, 2H), 8.21(m, 1H), 8.02~7.92(m, 9H), 7.66~7.32(m, 13H)
47	δ = 8.30~8.21(m, 7H), 8.02(d, 1H), 7.92~7.85(m, 4H), 7.66~7.25(m, 20H)
50	δ = 8.30~8.21(m, 8H), 8.02(d, 1H), 7.92~7.89(m, 2H), 7.66~7.32(m, 21H)
53	δ = 8.55(d, 1H), 8.30~8.21(m, 4H), 8.00~7.89(m, 8H), 7.59~7.25(m, 24H)
58	δ = 8.55(m, 1H), 8.41(d, 1H), 8.30~8.20(m, 7H), 8.11~8.02(m, 4H), 7.89~7.76(m, 7H), 7.54~7.32(m, 17H)
61	δ = 8.30(t, 2H), 8.21(d, 1H), 8.02(d, 1H), 7.79~7.32(m, 28H)
63	δ = 8.93(t, 3H), 8.30(t, 2H), 8.21(m, 1H), 8.12~7.54(m, 2H), 8.02(d, 1H), 7.93~7.82(m, 7H), 7.57~7.38(m, 12H)
67	δ = 8.40(t, 2H), 8.30(t, 2H), 8.21(m, 1H), 8.00~7.75(m, 9H), 7.54~7.16(m, 21H)
73	δ = 8.30~8.21(m, 8H), 8.02(d, 1H), 7.92~7.89(m, 2H), 7.79(m, 2H), 7.66(m, 2H), 7.54~7.32(m, 14H)
76	δ = 8.37~8.28(m, 6H), 8.02(d, 1H), 7.92~7.85(m, 4H), 7.66~7.32(m, 16H)
78	δ = 8.30~8.21(m, 8H), 8.02(d, 1H), 7.92~7.85(m, 4H), 7.66~7.32(m, 18H)
81	δ = 8.37~8.28(m, 6H), 8.02~7.89(m, 5H), 7.66~7.75(m, 5H), 7.54~7.32(m, 11H)
83	δ = 8.45(d, 1H), 8.37~8.28(m, 6H), 8.02~7.82(m, 6H), 7.66(t, 2H), 7.54~7.32(m, 12H)
86	δ = 8.55(d, 1H), 8.30~8.21(m, 8H), 8.02(d, 1H), 7.94~7.87(m, 4H), 7.66~7.25(m, 21H)
90	δ = 8.55(d, 1H), 8.37~8.28(m, 5H), 8.12(d, 1H), 8.02(m, 1H), 7.94~7.89(m, 3H), 7.66~7.32(m, 17H)
92	δ = 8.30~8.23(m, 8H), 8.02(d, 1H), 7.92~7.79(m, 6H), 7.66(m, 2H), 7.51~7.25(m, 16H)
95	δ = 8.30(m, 2H), 8.23~8.21(m, 2H), 8.02(m, 1H), 7.92~7.89(m, 2H), 7.79(m, 3H), 7.66(m, 2H), 7.54~7.32(m, 12H)
101	δ = 8.30~8.21(m, 8H), 8.02(d, 1H), 7.92~7.89(m, 2H), 7.79(t, 2H), 7.66(m, 2H), 7.54~7.32(m, 14H)
103	δ = 8.30~8.21(m, 5H), 8.02(d, 1H), 7.92~7.89(m, 2H), 7.79~7.25(m, 28H)
107	δ = 8.30(m, 2H), 8.02~7.89(m, 5H), 7.79~7.66(m, 7H), 7.51~7.32(m, 11H)
110	δ = 8.45(d, 1H), 8.30(m, 2H), 8.23~8.21(m, 2H), 7.98~7.79(m, 8H), 7.66(m, 2H), 7.52~7.32(m, 12H)
113	δ = 8.30~8.21(m, 6H), 8.02~7.89(m, 5H), 7.75~7.64(m, 7H), 7.54~7.32(m, 13H)
115	δ = 8.55(d, 1H), 8.30~8.23(m, 6H), 8.02(d, 1H), 7.94~7.87(m, 4H), 7.79~7.77(m, 3H), 7.69~7.32(m, 21H)
122	δ = 8.30~8.28(m, 7H), 8.12(d, 1H), 8.30(d, 1H), 7.92~7.89(m, 2H), 7.66(m, 1H), 7.54~7.32(m, 12H)
124	δ = 8.30~8.27(m, 3H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.85(m, 6H), 7.66(d, 1H), 7.52~7.25(m, 20H)
126	δ = 8.30~8.24(m, 6H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.89(m, 2H), 7.70~7.66(m, 2H), 7.54~7.32(m, 16H)
130	δ = 8.30~8.27(m, 5H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.81(m, 5H), 7.66(m, 2H), 7.54~7.32(m, 12H)
135	δ = 8.30~8.27(m, 5H), 8.12(d, 1H), 8.03(d, 1H), 7.95~7.85(m, 5H), 7.75(d, 1H), 7.66~7.64(m, 3H), 7.54~7.25(m, 13H)
138	δ = 8.55(d, 1H), 8.30~8.27(m, 5H), 8.12(d, 1H), 8.03(m, 1H), 7.94~7.85(m, 6H), 7.77(d, 1H), 7.69~7.33(m, 20H)
142	δ = 8.30~8.28(m, 5H), 8.12(m, 1H), 8.06~8.03(m, 2H), 7.92~7.87(m, 3H), 7.54~7.28(m, 25H)
144	δ = 8.30~8.28(m, 7H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.85(m, 4H), 7.66(m, 1H), 7.54~7.25(m, 22H)
147	δ = 9.15(d, 1H), 8.93(d, 1H), 8.30~8.27(m, 3H), 8.18~8.03(m, 5H), 7.89~7.82(m, 4H), 7.71~7.66(m, 3H), 7.54~7.32(m, 6H)
149	δ = 9.15(d, 1H), 8.93(m, 2H), 8.30~8.27(m, 3H), 8.18~8.03(m, 6H), 7.92~7.82(m, 6H), 7.66(d, 1H), 7.54~7.32(m, 6H)
152	δ = 8.30~8.27(m, 3H), 8.12(d, 1H), 7.03(d, 1H), 7.92~7.89(m, 2H), 7.66(m, 4H), 7.54~7.32(m, 20H)
155	δ = 8.88(d, 1H), 8.30~8.27(m, 5H), 8.12~8.03(m, 3H), 7.89~7.82(m, 4H), 7.66(m, 2H), 7.54~7.32(m, 9H)
161	δ = 8.30~8.27(m, 3H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.89(m, 2H), 7.66(m, 4H), 7.54~7.41(m, 16H)
164	δ = 8.45~8.41(m, 2H), 8.30(m, 2H), 8.20(m, 1H), 8.72(m, 1H), 8.03~7.89(m, 3H), 7.58~7.25(m, 14H)

TABLE 8-continued

NO	¹ H NMR (CDCl ₃ , 300 Mz)
168	δ = 8.30~8.27(m, 3H), 8.12(m, 1H), 8.03(m, 1H), 7.92~7.89(m, 2H), 7.66(m, 1H), 7.54~7.26(m, 14H), 7.11~6.98(m, 8H), 6.69(m, 4H), 6.51(t, 2H)
172	δ = 8.30~8.24(m, 8H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.89(t, 2H), 7.70~7.66(m, 2H), 7.57~7.32(m, 14H)
174	δ = 8.85(d, 1H), 8.38(d, 1H), 8.27(d, 1H), 8.12(m, 3H), 8.03~7.03(m, 6H), 7.66~7.50(m, 10H), 7.92~7.29(m, 4H)
178	δ = 8.55(m, 2H), 8.30~8.27(m, 3H), 8.12~8.03(m, 6H), 7.94~7.89(m, 4H), 7.66~7.25(m, 18H)
181	δ = 8.45(d, 1H), 8.30~8.24(m, 6H), 8.12(d, 1H), 8.03~7.98(m, 6H), 7.70~7.66(t, 2H), 7.57~7.32(m, 14H)
186	δ = 8.30~8.24(m, 4H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.81(m, 5H), 7.70~7.66(m, 3H), 7.57~7.32(m, 16H)
190	δ = 8.30~8.24(m, 6H), 8.12(m, 1H), 8.03(d, 1H), 7.92~7.85(m, 5H), 7.70~7.32(m, 17H)
194	δ = 9.09(d, 1H), 8.49~8.45(m, 2H), 8.30~8.27(m, 3H), 8.12(m, 1H), 8.00~7.89(m, 9H), 7.59~7.32(m, 12H)
198	δ = 8.56~8.55(m, 2H), 8.30~8.27(m, 3H), 8.12(m, 2H), 8.03(d, 1H), 7.94~7.88(m, 4H), 7.69~7.25(m, 14H)
201	δ = 8.30~8.27(m, 3H), 8.12(d, 1H), 8.03(d, 2H), 7.92~7.89(m, 2H), 7.66(m, 1H), 7.54~7.32(m, 7H), 7.21~7.16(m, 6H), 6.97~6.88(m, 4H), 6.59(d, 1H)
202	δ = 8.30~8.27(m, 3H), 8.12(m, 3H), 8.03(d, 1H), 7.92~7.89(m, 2H), 7.70~7.29(m, 19H)
206	δ = 8.27~8.23(m, 6H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.79(m, 7H), 7.66~7.32(m, 16H)
210	δ = 8.49(d, 1H), 8.30~8.27(m, 3H), 8.12~8.03(m, 7H), 7.92~7.89(m, 2H), 7.66~7.29(m, 18H)
214	δ = 8.30~8.27(m, 3H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.89(m, 2H), 7.70~7.66(m, 5H), 7.54~7.32(m, 19H)
218	δ = 8.30~8.24(m, 7H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.79(m, 6H), 7.70~7.66(m, 2H), 7.57~7.32(m, 16H)
221	δ = 8.30~8.23(m, 6H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.89(m, 3H), 7.75(d, 1H), 7.66~7.32(m, 15H)
222	δ = 8.30~8.23(m, 6H), 8.12(d, 1H), 8.03(m, 1H), 7.92~7.85(m, 4H), 7.66~7.32(m, 25H)
226	δ = 8.30~8.23(m, 8H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.85(m, 6H), 7.66~7.32(m, 15H)
230	δ = 8.55(d, 1H), 8.30~8.28(m, 8H), 8.12(d, 1H), 8.03(d, 1H), 7.94~7.85(m, 6H), 7.77(d, 1H), 7.69~7.25(m, 18H)
234	δ = 8.55(d, 1H), 8.30~8.23(m, 6H), 8.12(d, 1H), 8.03(m, 1H), 7.94~7.87(m, 4H), 7.77(d, 1H), 7.69~7.25(m, 18H)
238	δ = 8.30~8.23(m, 8H), 8.12(d, 1H), 8.03(d, 1H), 7.89~7.85(m, 4H), 7.66(d, 1H), 7.54~7.32(m, 14H)
241	δ = 8.30~8.23(m, 5H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.89(m, 2H), 7.75~7.66(m, 4H), 7.57~7.32(m, 20H)
242	δ = 8.30~8.23(m, 8H), 8.12(d, 1H), 8.03(m, 1H), 7.92~7.79(m, 6H), 7.66(d, 1H), 7.54~7.25(m, 16H)
246	δ = 8.30~8.23(m, 6H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.85(m, 4H), 7.66~7.32(m, 15H)
250	δ = 8.30~8.28(m, 8H), 8.12(d, 1H), 8.03(m, 1H), 7.89~7.85(m, 6H), 7.66~7.32(m, 15H)
254	δ = 8.55(d, 1H), 8.30~8.23(m, 8H), 8.12(d, 1H), 8.03(d, 1H), 7.94~7.85(m, 6H), 7.77(d, 1H), 7.66~7.25(m, 18H)
258	δ = 8.55(d, 1H), 8.30~8.28(m, 6H), 8.12(d, 1H), 8.03(d, 1H), 7.94~7.87(m, 4H), 7.77(d, 1H), 7.58~7.25(m, 18H)
261	δ = 8.30~8.23(m, 4H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.79(m, 8H), 7.66(m, 1H), 7.54~7.32(m, 14H)
262	δ = 8.30~8.23(m, 4H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.79(m, 6H), 7.66~7.32(m, 15H)
266	δ = 8.45(d, 1H), 8.30~8.23(m, 4H), 8.12~7.79(m, 10H), 7.66(m, 1H), 7.54~7.32(m, 11H)
270	δ = 2.34~8.23(m, 5H), 8.12(d, 1H), 8.03(d, 1H), 7.92~7.32(m, 13H), 7.54~7.32(m, 12H)
274	δ = 8.55(d, 1H), 8.30~8.23(m, 6H), 8.12(d, 1H), 8.03(d, 1H), 7.94~7.79(m, 9H), 7.66~7.25(m, 18H)
278	δ = 8.30~8.23(m, 4H), 8.12(d, 1H), 8.06~8.03(m, 2H), 7.92~7.87(m, 3H), 7.79(m, 2H), 7.66~7.28(m, 16H), 1.72(s, 2H)
280	δ = 8.30~8.28(m, 7H), 8.04(d, 1H), 7.92~7.89(m, 3H), 7.66(d, 1H), 7.54~7.41(m, 12H)
282	δ = 8.30(m, 2H), 8.21(d, 1H), 8.04(d, 1H), 7.92~7.85(m, 6H), 7.56(d, 1H), 7.54~7.25(m, 20H)
286	δ = 8.55(m, 2H), 8.45(d, 1H), 8.30~8.21(m, 5H), 8.01~7.82(m, 10H), 7.66(d, 1H), 7.55~7.41(m, 13H)
290	δ = 8.30~8.21(m, 5H), 8.04(d, 1H), 7.92~7.85(m, 7H), 7.66(d, 1H), 7.54~7.25(m, 18H)
294	δ = 8.30~8.21(m, 5H), 8.04(d, 1H), 7.90~7.81(m, 8H), 7.66(m, 2H), 7.54~7.25(m, 14H)

TABLE 8-continued

NO	¹ H NMR (CDCl ₃ , 300 Mz)
298	δ = 8.55(d, 1H), 8.30~8.21(m, 5H), 8.04(m, 1H), 7.94~7.87(m, 5H), 7.77(s, 1H), 7.66~7.25(m, 18H)
301	δ = 8.55(d, 1H), 8.42(d, 1H), 8.28~8.21(m, 5H), 8.08~8.04(m, 3H), 7.92~7.79(m, 7H), 7.66~7.41(m, 17H)
302	δ = 8.28~8.21(m, 6H), 8.04(d, 1H), 7.92~7.85(m, 5H), 7.70~7.66(m, 2H), 7.51~7.25(m, 18H)
306	δ = 8.55(d, 1H), 8.30~8.21(m, 5H), 8.12(d, 1H), 8.04(d, 1H), 7.94~7.85(m, 6H), 7.66~7.25(m, 17H)
310	δ = 8.30(m, 2H), 8.21~8.04(m, 5H), 7.92~7.82(m, 5H), 7.71~7.66(m, 3H), 7.54~7.32(m, 6H)
314	δ = 8.93(m, 2H), 8.30(m, 2H), 8.21(d, 1H), 8.12~8.04(m, 2H), 7.92~7.82(m, 8H), 7.66(m, 1H), 7.54~7.25(m, 10H)
318	δ = 8.30~8.21(m, 5H), 8.09~8.04(m, 2H), 7.92~7.82(m, 5H), 7.66(m, 2H), 7.54~7.32(m, 10H)
321	δ = 8.45(m, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.11~7.98(m, 8H)
322	δ = 8.30(m, 2H), 7.92~7.82(m, 3H), 7.66(m, 1H), 7.54~7.02(m, 6H), 7.32~7.02(m, 4H), 6.80~6.73(m, 3H), 6.55(m, 2H), 1.72(m, 6H)
326	δ = 8.30(m, 2H), 8.21(m, 2H), 8.04(m, 1H), 7.92~7.81(m, 6H), 7.72~7.66(m, 3H), 7.54~7.25(m, 16H)
330	δ = 8.49(m, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.12~8.04(m, 3H), 7.92~7.89(m, 3H), 7.58~7.25(m, 20H)
334	δ = 8.53(m, 2H), 8.30(m, 2H), 8.21(m, 1H), 8.04(m, 1H), 7.92~7.89(m, 3H), 7.70~7.66(m, 3H), 7.54~7.25(m, 10H), 7.14(m, 2H)
338	δ = 8.30~8.16(m, 6H), 8.04(m, 1H), 7.92~7.83(m, 5H), 7.66~7.41(m, 11H)
341	δ = 9.15(d, 1H), 8.92(m, 2H), 8.30(m, 2H), 8.21~8.04(m, 6H), 7.90~7.82(m, 7H), 7.66(m, 1H), 7.54~7.38(m, 6H)
342	δ = 9.15(d, 1H), 8.93(m, 1H), 8.30(m, 2H), 8.21~8.04(m, 5H), 7.92~7.82(m, 5H), 7.66~7.71(m, 3H), 7.54~7.32(m, 6H)
346	δ = 8.93(m, 2H), 8.30(m, 2H), 8.21(m, 1H), 8.12~8.04(m, 3H), 7.93~7.82(m, 8H), 7.66(m, 1H), 7.54~7.25(m, 10H)
350	δ = 8.88(s, 1H), 8.30~8.21(m, 5H), 8.09~8.04(m, 2H), 7.92~7.82(m, 5H), 7.66(m, 2H), 7.54~7.32(m, 9H)
354	δ = 8.30(m, 2H), 7.92~7.82(m, 3H), 7.66(m, 1H), 7.54~7.26(m, 12H), 7.11~7.02(m, 8H), 6.80(m, 1H), 6.69(m, 2H), 6.51(m, 2H)
358	δ = 8.55(m, 2H), 8.30(m, 2H), 8.21(m, 1H), 8.12~8.04(m, 4H), 7.94~7.90(m, 5H), 7.63~7.29(m, 18H)
361	δ = 8.30(m, 2H), 8.21(m, 1H), 8.04(m, 1H), 7.92~7.89(m, 3H), 7.66(m, 1H), 7.54~7.32(m, 8H), 6.92~6.89(m, 4H), 6.77~6.69(m, 4H)
362	δ = 8.55(d, 1H), 8.21(m, 2H), 8.12(m, 1H), 8.04(m, 1H), 7.92~7.82(m, 5H), 7.71(m, 5H), 7.54~7.50(m, 3H), 7.38~7.32(m, 2H), 7.21~7.16(m, 6H), 6.97(m, 2H), 6.69(m, 2H)
366	δ = 8.30~8.21(m, 6H), 8.04(d, 1H), 7.92~7.85(m, 5H), 7.70(m, 1H), 7.66~7.32(m, 18H)
370	δ = 8.30~8.21(m, 4H), 8.04(d, 1H), 7.92~7.85(m, 6H), 7.70~7.66(m, 3H), 7.54~7.32(m, 16H)
374	δ = 8.28~8.21(m, 6H), 8.04(d, 1H), 7.92~7.81(m, 6H), 7.66~7.32(m, 17H)
378	δ = 8.55(m, 1H), 8.30~8.21(m, 4H), 8.00~7.87(m, 9H), 7.66~7.25(m, 23H)
381	δ = 8.30(d, 2H), 8.21(d, 1H), 8.04(d, 1H), 7.92~7.89(m, 3H), 7.66(m, 1H), 7.54~7.32(m, 7H), 7.05~7.02(m, 4H), 6.89~6.88(m, 2H), 6.73(m, 2H), 6.59~6.55(m, 3H), 1.72(s, 6H)
382	δ = 8.30(m, 2H), 8.21(m, 1H), 8.04(d, 1H), 7.90~7.89(m, 3H), 7.66(m, 1H), 7.54~7.32(m, 7H), 6.92~6.88(m, 6H), 6.77(m, 2H), 6.59(m, 3H)
386	δ = 8.30~8.21(m, 7H), 8.10~8.06(m, 3H), 7.92~7.89(m, 3H), 7.81(d, 1H), 7.66~7.32(m, 14H)
390	δ = 8.55(m, 1H), 8.30(m, 2H), 8.21(d, 1H), 8.08~8.04(m, 2H), 7.92~7.81(m, 9H), 7.66(m, 1H), 7.55~7.32(m, 15H)
394	δ = 8.49(d, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.12~8.04(m, 3H), 7.92~7.89(m, 3H), 7.57~7.29(m, 20H)
398	δ = 8.30(m, 2H), 8.21(d, 1H), 8.04(d, 1H), 7.92~7.89(m, 3H), 7.66(m, 3H), 7.57~7.32(m, 20H)
401	δ = 8.30~8.21(m, 6H), 8.04(m, 1H), 7.90~7.79(m, 11H), 7.66(m, 1H), 7.54~7.41(m, 14H)
402	δ = 8.30~8.21(m, 8H), 8.04(m, 1H), 7.90~7.79(m, 7H), 7.66(d, 1H), 7.54~7.25(m, 16H)
406	δ = 8.30~8.21(m, 6H), 8.04(d, 1H), 7.92~7.89(m, 5H), 7.66~7.32(m, 15H)
410	δ = 8.30~8.23(m, 8H), 8.04(d, 1H), 7.95~7.85(m, 7H), 7.75(m, 1H), 7.66~7.64(m, 3H), 7.54~7.32(m, 11H)
414	δ = 8.55(d, 1H), 8.30~8.21(m, 8H), 8.04(d, 1H), 7.94~7.87(m, 7H), 7.77(d, 1H), 7.66~7.25(m, 18H)
418	δ = 8.55(m, 1H), 8.30~8.21(m, 5H), 8.12(d, 1H), 8.04(d, 1H), 7.94~7.90(m, 4H), 7.66~7.25(m, 16H)
421	δ = 8.30~8.23(m, 5H), 8.04(d, 1H), 7.92~7.90(m, 3H), 7.79(m, 4H), 7.70~7.66(m, 2H), 7.57~7.25(m, 23H)
422	δ = 8.45(d, 1H), 8.30(m, 2H), 8.23~8.21(m, 2H), 8.08~7.82(m, 10H), 7.66(d, 1H), 7.54~7.41(m, 11H)
426	δ = 8.30~8.21(m, 4H), 8.04(d, 1H), 7.89~7.79(m, 7H), 7.66~7.32(m, 15H)
430	δ = 8.30~8.21(m, 6H), 8.04(d, 1H), 7.85~7.79(m, 10H), 7.66(m, 2H), 7.54~7.32(m, 10H)

TABLE 8-continued

NO	¹ H NMR (CDCl ₃ , 300 Mz)
446	8.45(m, 1H), 8.30(d, 2H), 8.21(d, 1H), 7.85(m, 8H), 7.66(t, 1H), 7.54~7.50(m, 16H), 7.25(m, 4H)
450	8.55(d, 1H), 8.45(d, 1H), 8.30~8.21(m, 5H), 8.02~7.87(m, 5H), 7.77(d, 1H), 7.52~7.25(m, 18H)
454	8.45(m, 1H), 8.30~8.21(m, 5H), 8.06~7.87(m, 7H), 7.61~7.41(m, 14H), 7.28~7.25(m, 3H)
458	8.45(d, 1H), 8.30~8.21(m, 5H), 8.02~7.81(m, 8H), 7.66(m, 2H), 7.54~7.32(m, 24H)
462	9.15(s, 1H), 8.93(d, 1H), 8.45(d, 1H), 8.30(m, 2H), 8.21~7.98(m, 9H), 8.12~7.82(m, 9H), 7.71~7.66(m, 3H), 7.54~7.47(m, 6H)
466	8.93(d, 1H), 8.45(d, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.12(d, 2H), 8.02~7.82(m, 8H), 7.66(s, 1H), 7.54~7.74(m, 6H), 7.25(s, 4H)
470	8.88(s, 1H), 8.45(d, 1H), 8.30()
474	8.88(s, 1H), 8.45(d, 1H), 8.30(m, 2H), 8.21(d, 1H), 8.09(s, 1H), 8.02~7.92(m, 2H), 7.84~7.82(m, 2H), 7.66(m, 2H), 7.54~7.47(m, 9H)
478	8.45(d, 1H), 8.30(m, 2H), 8.21(d, 1H), 7.98~7.75(m, 7H), 7.66(m, 1H), 7.57~7.28(m, 16H)
482	8.25(d, 1H), 8.30~8.28(m, 6H), 8.02~7.81(m, 6H), 7.72~7.66(m, 3H), 7.54~7.41(m, 13H)
486	8.88(d, 1H), 8.45(d, 1H), 8.30(m, 4H), 8.10~8.06(m, 4H), 7.98~7.92(m, 2H), 7.81(m, 1H), 7.69(m, 1H), 7.54~7.47(m, 8H), 7.35(d, 2H)
490	8.45(d, 1H), 8.30(m, 2H), 8.21(d, 1H), 8.12(m, 1H), 8.02~7.92(m, 3H), 7.63~7.50(m, 13H), 7.29(m, 2H)
494	8.45(d, 1H), 8.30(m, 2H), 8.21(m, 2H), 8.12(m, 2H), 7.98
498	9.09(s, 1H), 8.49~8.45(m, 2H), 8.30~8.21(m, 7H), 8.04~7.92(m, 8H), 7.73(m, 3H), 7.58~7.41(m, 15H)
502	8.55(d, 1H), 8.45(d, 1H), 8.30~8.21(m, 4H), 8.00~7.87(m, 8H), 7.77~7.45(m, 21H), 7.33~7.25(m, 2H)
506	8.45(d, 1H), 8.30~8.21(m, 6H), 8.02~7.92(m, 3H), 7.70~7.41(m, 26H)
510	8.45(d, 1H), 8.30~8.21(m, 8H), 8.02~7.92(m, 3H), 7.54~7.41(m, 16H), 7.25(s, 4H)
514	8.45(d, 2H), 8.30~8.21(m, 6H), 8.02~7.94(m, 5H), 7.82(m, 1H), 7.66~7.41(m, 16H)
518	8.45~8.41(m, 2H), 8.30~8.21(m, 6H), 8.00~7.86(m, 9H), 7.58~7.41(m, 18H)
522	8.55(d, 1H), 8.45(d, 1H), 8.37~8.28(m, 6H), 8.02~7.87(m, 5H), 7.77(s, 1H), 7.69~7.33(m, 18H)
526	8.45(d, 1H), 8.30~8.21(m, 6H), 8.02~7.92(m, 3H), 7.79~7.48(m, 20H), 7.25(s, 4H)
530	8.45(d, 1H), 8.30~8.21(m, 6H), 8.02~7.92(m, 3H), 7.75~7.41(m, 19H), 7.25(s, 4H)
534	8.55(d, 1H), 8.45(d, 1H), 8.30~8.21(m, 8H), 8.02~7.92(m, 5H), 7.77(s, 1H), 7.66~7.25(m, 20H)
538	8.45(d, 1H), 8.30(m, 2H), 8.23~8.21(m, 2H), 8.02~7.79(m, 7H), 7.66~7.32(m, 15H)
542	8.45(d, 1H), 8.30(m, 2H), 8.23~8.21(m, 2H), 8.02~7.92(m, 3H), 7.79(m, 4H), 7.66(m, 1H), 7.54~7.41(m, 12H)
546	8.45(d, 1H), 8.30~8.21(m, 6H), 8.02~7.89(m, 4H), 7.79~7.75(m, 3H), 7.66~7.38(m, 17H)
550	8.45(d, 1H), 8.30~8.21(m, 6H), 8.02~7.95(m, 5H), 7.79~7.75(m, 3H), 7.66~7.64(m, 2H), 7.54~7.32(m, 13H)
554	8.45(d, 1H), 8.30~8.27(m, 5H), 8.12(d, 1H), 7.85~7.98(m, 5H), 7.52~7.41(m, 14H), 7.25(d, 2H)
558	8.45(d, 2H), 8.30(m, 4H), 8.23~8.21(m, 2H), 8.02~7.92(m, 5H), 7.79~7.82(m, 3H), 7.66(m, 1H), 7.54~7.41(m, 12H), 7.25(m, 2H)
562	8.45(s, 1H), 8.30~8.27(m, 5H), 8.12(m, 1H), 7.98~7.81(m, 6H), 7.66(m, 1H), 7.54~7.32(m, 12H)
566	8.45(d, 1H), 8.30~8.27(m, 5H), 8.12(m, 1H), 8.03~7.81(m, 8H), 7.66(m, 1H), 7.54~7.32(m, 14H)
570	8.45(d, 2H), 8.28~8.27(m, 5H), 8.12(d, 1H), 8.03~7.82(m, 8H), 7.56~7.41(m, 12H), 7.25(m, 2H)
574	8.55(m, 1H), 8.45(m, 1H), 8.30~8.27(m, 5H), 8.12(m, 2H), 8.03~7.92(m, 4H), 7.63(m, 1H), 7.54~7.25(m, 13H)
578	9.15(s, 1H), 8.93(m, 2H), 8.45(m, 1H), 8.30~8.27(m, 3H), 8.03~7.82(m, 12H), 7.54~7.41(m, 6H)
582	8.45(m, 2H), 8.30(m, 2H), 8.11~7.98(m, 8H), 7.54~7.47(m, 8H)
586	9.30(d, 1H), 9.15(s, 2H), 8.99(m, 1H), 8.81(s, 1H), 8.53(m, 1H), 8.45(m, 1H), 8.30~8.27(m, 3H), 8.12(m, 1H), 8.03~7.88(m, 4H), 7.70(m, 1H), 7.54~7.41(m, 11H), 7.14(m, 1H)
590	8.45(m, 1H), 8.30~8.27(m, 7H), 8.12(m, 1H), 8.03~7.81(m, 8H), 7.71~7.72(m, 2H), 7.54~7.41(m, 13H)
594	8.88(s, 1H), 8.45(d, 1H), 8.30~8.27(m, 5H), 8.12~7.98(m, 5H), 7.84~7.82(d, 2H), 7.66(s, 1H), 7.54~7.47(m, 9H)
598	8.55(m, 1H), 8.43(d, 1H), 8.30~8.27(m, 3H), 8.12(m, 2H), 8.03~7.92(m, 4H), 7.79(m, 1H), 7.68~7.25(m, 11H), 7.52~7.29(m, 3H)

TABLE 8-continued

NO	¹ H NMR (CDCl ₃ , 300 Mz)
602	8.45(m, 1H), 8.30~8.27(m, 3H), 8.12(m, 1H), 8.03~7.98(m, 3H), 7.54~7.47(m, 8H), 7.05~7.02(m, 4H), 6.79~6.69(m, 4H), 6.55(m, 2H), 1.72(s, 2H)
606	8.45(d, 1H), 8.27~8.30(m, 3H), 8.12(m, 1H), 7.98~7.75(m, 7H), 7.54~7.19(m, 16H)
610	8.72(m, 1H), 8.57(m, 1H), 8.45~8.41(m, 2H), 8.30~8.22(m, 6H), 8.10~7.92(m, 10H), 7.81(m, 1H), 7.73(m, 2H), 7.58~7.50(m, 11H), 7.35(m, 2H)
614	8.55(m, 1H), 8.45(m, 1H), 8.30~8.24(m, 4H), 8.12(m, 1H), 8.00~7.87(m, 8H), 7.77~7.69(m, 4H), 7.59~7.50(m, 16H), 7.33~7.25(m, 2H)
618	8.55(m, 1H), 8.45(d, 1H), 8.30~8.24(m, 6H), 8.12(m, 1H), 8.03~7.92(m, 5H), 7.77(m, 1H), 7.70~7.69(m, 2H), 7.58~7.25(m, 18H)
622	8.45(d, 1H), 8.30~8.24(m, 4H), 8.12(m, 1H), 7.85~7.98(m, 7H), 7.70(d, 1H), 7.57~7.41(m, 18H), 7.25(m, 4H)
626	8.45(d, 1H), 8.27~8.24(m, 4H), 8.12(d, 1H), 8.03~7.81(m, 6H), 7.66(m, 2H), 7.57~7.32(m, 16H)
630	8.55(d, 1H), 8.45~8.41(m, 2H), 8.30~8.28(m, 8H), 8.03~7.80(m, 10H), 7.55~7.41(m, 15H)
634	8.45(m, 1H), 8.28~8.24(m, 6H), 8.12(d, 1H), 8.03~7.81(m, 6H), 7.70~7.66(m, 2H), 7.57~7.32(m, 15H)
638	8.49~8.45(m, 2H), 8.30~8.27(m, 3H), 8.12~7.92(m, 6H), 7.70(m, 1H), 7.58~7.45(m, 17H), 7.29(m, 1H)
642	8.45(d, 1H), 8.30~8.27(m, 3H), 8.12(m, 1H), 8.03~7.92(m, 3H), 7.54~7.44(m, 7H), 6.92~6.88(m, 6H), 6.77(m, 2H), 6.59(m, 3H)
646	8.45(d, 1H), 8.30~8.26(m, 7H), 8.10~7.92(m, 7H), 7.81(m, 1H), 7.54~7.47(m, 11H)
650	8.92(m, 2H), 8.45(d, 1H), 8.30~8.27(m, 3H), 8.12(m, 3H), 8.03~7.82(m, 8H), 7.70(d, 1H), 7.57~7.48(m, 9H)
654	8.45(d, 2H), 8.28~8.23(m, 6H), 8.12(d, 1H), 8.03~7.92(m, 4H), 7.82(m, 1H), 7.52~7.41(m, 12H)
658	8.45(m, 2H), 8.30~8.23(m, 8H), 8.12(m, 1H), 7.98~7.85(m, 8H), 7.56~7.41(m, 12H)
662	8.45(m, 1H), 8.30~8.23(m, 8H), 8.12(d, 1H), 8.03~7.85(m, 5H), 7.54~7.41(m, 14H)
666	8.45(d, 1H), 8.30~8.23(m, 8H), 8.12(m, 1H), 8.03~7.85(m, 7H), 7.54~7.47(m, 12H), 7.25(s, 4H)
670	8.45(d, 1H), 8.30~8.23(m, 6H), 8.12(d, 1H), 8.03~7.92(m, 5H), 7.75(d, 1H), 7.66~7.64(m, 2H), 7.54~7.38(m, 11H)
674	8.45(d, 1H), 8.30~8.23(m, 4H), 8.12(d, 1H), 8.03~7.79(m, 7H), 7.54~7.32(m, 15H)
678	8.55(d, 1H), 8.45(d, 1H), 8.30~8.23(m, 4H), 8.12(d, 1H), 8.03~7.87(m, 5H), 7.79~7.77(m, 3H), 7.69(d, 1H), 7.58~7.41(m, 16H)
682	8.45(d, 1H), 8.30~8.23(m, 8H), 8.12(d, 1H), 7.98~7.79(m, 7H), 7.54~7.41(m, 12H)
686	8.45(d, 1H), 8.30~8.23(m, 4H), 8.12(d, 1H), 8.03~7.89(m, 4H), 7.79~7.75(m, 3H), 7.66~7.38(m, 15H)
690	8.45(d, 1H), 8.30~8.23(m, 6H), 8.12(d, 1H), 7.92~7.79(m, 10H), 7.66(d, 1H), 7.54~7.32(m, 12H)
694	8.45(d, 1H), 8.30~8.23(m, 9H), 8.12(d, 1H), 8.03~7.85(m, 5H), 7.75~7.70(m, 2H), 7.54~7.41(m, 16H)
698	8.45(d, 1H), 8.30~8.23(m, 6H), 8.12(d, 1H), 8.06~7.79(m, 8H), 7.61~7.41(m, 13H), 7.28(m, 1H), 1.72(m, 6H)
702	8.45(d, 1H), 8.30~8.21(m, 7H), 8.04~7.85(m, 6H), 7.54~7.41(m, 12H), 7.25(m, 2H)
706	8.45(d, 1H), 8.30~8.21(m, 5H), 8.04~7.58(m, 7H), 7.66(d, 1H), 7.54~7.32(m, 15H)
710	8.45(d, 1H), 8.30~8.21(m, 5H), 8.04~7.81(m, 9H), 7.66(m, 1H), 7.54~7.32(m, 15H)
714	8.55(d, 1H), 8.45(m, 1H), 8.30~8.21(m, 5H), 8.04~7.85(m, 8H), 7.77(d, 1H), 7.69(d, 1H), 7.58~7.25(m, 18)
718	8.55(d, 1H), 8.45(d, 1H), 8.30~8.21(m, 5H), 8.12(m, 1H), 8.04~7.92(m, 5H), 7.63(m, 1H), 7.54~7.25(m, 13H)
722	8.45(d, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.044~7.92(m, 4H), 7.66(s, 3H), 7.54~7.41(m, 16H), 7.25(d, 4H)
726	8.83(m, 2H), 8.45~8.38(m, 4H), 8.21(m, 1H), 8.04~7.90(m, 4H), 7.58~7.47(m, 9H)
730	8.88(s, 1H), 8.45(d, 1H), 8.30(m, 4H), 8.21(m, 1H), 7.90~7.82(m, 7H), 7.66(s, 1H), 7.54~7.47(m, 9H)
734	8.49~8.45(m, 2H), 8.30(m, 2H), 8.21(m, 1H), 8.12~7.90(m, 6H), 7.63~7.45(m, 14H), 7.29~7.25(m, 5H)
738	8.45(m, 2H), 8.30(m, 2H), 7.98~7.92(m, 2H), 7.54~7.47(m, 6H), 7.33~7.26(m, 6H), 7.11~6.98(m, 6H), 6.80(s, 1H), 6.69(m, 2H), 6.51(m, 2H)
742	9.09(s, 2H), 8.49~8.45(m, 3H), 8.30(m, 2H), 8.21(m, 1H), 8.04~7.85(m, 12H), 7.59~7.54(m, 10H), 7.25(m, 2H)
746	8.45(d, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.04~7.85(m, 7H), 7.75(m, 1H), 7.66~7.25(m, 18H)

TABLE 8-continued

NO	¹ H NMR (CDCl ₃ , 300 Mz)
750	9.09(s, 1H), 8.49~8.45(m, 3H), 8.30(m, 2H), 8.21(m, 1H), 8.04~7.94(m, 9H), 7.82(m, 1H), 7.59~7.47(m, 11H)
754	8.45(d, 1H), 8.30~8.21(m, 6H), 8.04~7.81(m, 7H), 7.70~7.66(m, 2H), 7.57~7.32(m, 14H)
758	8.55(m, 1H), 8.45(m, 1H), 8.30~8.21(m, 6H), 8.04~7.87(m, 6H), 7.77(s, 1H), 7.70~7.69(m, 2H), 7.58~7.41(m, 18H)
762	8.45(m, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.04~7.92(m, 4H), 7.54~7.44(m, 7H), 7.05~7.02(m, 4H), 6.89~6.88(m, 2H), 6.73(m, 2H), 6.55(m, 2H)
766	8.45(d, 1H), 8.30~8.28(m, 6H), 7.79~7.75(m, 8H), 7.54~7.41(m, 15H)
770	8.49~8.45(m, 2H), 8.30(m, 2H), 8.21(m, 1H), 8.12~7.90(m, 6H), 7.70(s, 1H), 7.58~7.45(m, 17H), 7.29(m, 1H)
774	8.45~8.41(m, 3H), 8.30(m, 2H), 8.21~8.20(m, 2H), 8.04~7.98(m, 4H), 7.70(m, 1H), 7.54~7.41(m, 12H)
778	8.45(d, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.12(m, 2H), 8.04~7.90(m, 4H), 7.70(s, 1H), 7.63~7.47(m, 15H), 7.29(m, 2H)
782	8.45(d, 1H), 8.30~8.21(m, 5H), 8.04~7.92(m, 4H), 7.75~7.70(m, 3H), 7.57~7.41(m, 20H)
786	8.41~8.54(m, 2H), 8.30~8.21(m, 6H), 8.04~7.75(m, 11H), 7.57~7.41(m, 15H)
790	8.45(d, 1H), 8.30~8.21(m, 7H), 8.10~7.90(m, 7H), 7.81(d, 1H), 7.60~7.54(m, 11H)
794	8.45(d, 1H), 8.30~8.21(m, 8H), 8.11~7.98(m, 10H), 7.54~7.41(m, 11H)
898	8.55(m, 1H), 8.45(m, 1H), 8.30~8.21(m, 7H), 8.12(m, 1H), 8.04~7.92(m, 7H), 7.63(m, 1H), 7.54~7.25(m, 14H)
802	8.55(m, 1H), 8.45(d, 1H), 8.30~8.21(m, 6H), 8.04~7.94(m, 6H), 7.77(s, 1H), 7.69(d, 1H), 7.58~7.25(m, 16H)
806	8.45(d, 1H), 8.30(m, 2H), 8.23~8.21(m, 2H), 8.04~7.89(m, 6H), 7.79~7.75(m, 3H), 7.66~7.64(m, 2H), 7.54~7.38(m, 10H)
810	8.55(d, 1H), 8.45(m, 1H), 8.30~8.21(m, 5H), 8.12(m, 1H), 8.04~7.92(m, 5H), 7.63(m, 1H), 7.54~7.25(m, 14H)
814	8.45(d, 1H), 8.30~8.23(m, 7H), 8.04~7.85(m, 6H), 7.75~7.70(m, 3H), 7.57~7.41(m, 20H)
818	8.45(d, 1H), 8.30(m, 2H), 8.23~8.21(m, 2H), 8.04~7.94(m, 6H), 7.82~7.79(m, 3H), 7.54~7.41(m, 12H)
822	8.55(m, 1H), 8.45(d, 1H), 8.30(m, 2H), 8.21(m, 1H), 8.12(m, 1H), 8.04~7.90(m, 5H), 7.79(m, 2H), 7.63(m, 1H), 7.54~7.25(m, 14H)
826	8.45(m, 1H), 8.300~8.21(m, 6H), 8.04~7.79(m, 11H), 7.66(m, 1H), 7.54~7.32(m, 12H)
830	8.78(m, 2H), 8.50~8.45(m, 3H), 8.28~8.23(m, 6H), 7.85~7.79(m, 8H), 7.51~7.41(m, 10H)


EXPERIMENTAL EXAMPLE

Experimental Example 1

1) Manufacture of Organic Light Emitting Device

A glass substrate on which indium tin oxide (ITO) was coated as a thin film to a thickness of 1,500 Å was cleaned with distilled water ultrasonic waves. After the cleaning with distilled water was finished, the substrate was ultrasonic cleaned with solvents such as acetone, methanol and isopropyl alcohol, then dried, and UVO treatment was conducted for 5 minutes using UV in a UV cleaner. After that, the substrate was transferred to a plasma cleaner (PT), and after conducting plasma treatment under vacuum for ITO work function and residual film removal, the substrate was transferred to a thermal deposition apparatus for organic deposition. On the transparent ITO electrode (anode), organic materials were formed in a single stack structure. The following HAT-CN was deposited to a thickness of 50 Å as a hole injection layer, and, as a hole transfer layer, DNTPD was doped to NPD by 10% or less and then deposited and formed to a thickness of 1500 Å, and TCTA was continuously deposited to a thickness of 200 Å. Subsequently, a light emitting layer including a t-Bu-peryrene


dopant in an ADN host was formed to a thickness of 250 Å. Then, Alq₃, an electron transfer layer, was formed as a film to a thickness of 250 Å, and as an N-type charge generation layer, a compound described in the following Table 9 was doped with lithium, an alkali metal, to be formed as a film to a thickness of 100 Å. Then, Al, a cathode, was formed as a film to a thickness of approximately 1,000 Å, and as a result, an organic light emitting device was manufactured.




HAT-CN

497

-continued




NPD




DNTPD

498


-continued




TCTA



ADN



t-Bu-Perylene




Alq3

50

55

60






65



A

499

-continued



500

2) Driving Voltage and Light Emission Efficiency of Organic Light Emitting Device

For each of the organic light emitting devices manufactured as above, electroluminescent (EL) properties were measured using M7000 manufactured by McScience Inc., and with the measurement results, T_{95} was measured when standard luminance was 750 cd/m^2 through a lifetime measurement system (M6000) manufactured by McScience Inc. Results of measuring driving voltage, light emission efficiency, external quantum efficiency and color coordinate (CIE) of the white organic electroluminescent devices manufactured according to the present disclosure are as shown in Table 9.

TABLE 9

				Light			
		Compound	Driving Voltage (V)	Emission Efficiency (cd/A)	CIE (x, y)	Life-time (T ₉₅)	
D	20	Example 1-1	1	4.53	7.21	(0.134, 0.104)	43
		Example 1-2	4	4.18	7.13	(0.134, 0.104)	45
		Example 1-3	8	4.27	7.30	(0.134, 0.105)	39
		Example 1-4	12	4.21	6.98	(0.134, 0.103)	41
	25	Example 1-5	15	4.97	6.56	(0.134, 0.101)	37
		Example 1-6	18	4.57	7.00	(0.134, 0.101)	44
		Example 1-7	21	5.12	6.48	(0.133, 0.102)	34
		Example 1-8	25	4.32	7.11	(0.134, 0.100)	42
		Example 1-9	28	5.11	6.42	(0.133, 0.101)	30
	30	Example 1-10	32	5.27	6.55	(0.134, 0.101)	28
Example 1-11		35	5.68	6.42	(0.134, 0.101)	32	
Example 1-12		38	5.88	6.30	(0.134, 0.101)	30	
Example 1-13		41	5.14	6.51	(0.133, 0.101)	28	
Example 1-14		44	5.89	6.18	(0.133, 0.102)	80	
Example 1-15		47	5.90	6.11	(0.134, 0.100)	78	
Example 1-16		50	5.28	6.78	(0.133, 0.101)	27	
Example 1-17		53	5.44	6.37	(0.134, 0.101)	26	
35		Example 1-18	58	5.68	6.32	(0.133, 0.100)	37
		Example 1-19	61	5.40	6.48	(0.134, 0.100)	25
	Example 1-20	63	5.38	6.50	(0.133, 0.101)	28	
	Example 1-21	67	5.33	6.48	(0.134, 0.101)	28	
	Example 1-22	73	5.36	6.54	(0.134, 0.099)	27	
E	40	Example 1-23	76	5.34	6.55	(0.134, 0.101)	30
		Example 1-24	78	5.68	6.43	(0.133, 0.101)	31
		Example 1-25	81	5.44	6.40	(0.134, 0.102)	33
		Example 1-26	83	5.67	6.39	(0.134, 0.101)	35
		Example 1-27	86	4.87	5.99	(0.132, 0.101)	29
	45	Example 1-28	90	5.68	6.47	(0.134, 0.103)	31
		Example 1-29	92	5.68	6.50	(0.134, 0.101)	34
		Example 1-30	95	5.66	6.77	(0.133, 0.102)	29
		Example 1-31	101	5.73	6.41	(0.133, 0.101)	54
		Example 1-32	103	5.64	6.40	(0.134, 0.100)	32
50	Example 1-33	107	5.71	6.52	(0.134, 0.101)	33	
	Example 1-34	110	5.68	6.55	(0.133, 0.100)	30	
	Example 1-35	113	5.70	6.40	(0.133, 0.101)	30	
	Example 1-36	115	5.23	6.33	(0.133, 0.101)	31	
	Example 1-37	122	5.78	6.44	(0.133, 0.101)	37	
	Example 1-38	124	5.73	6.62	(0.133, 0.099)	31	
	Example 1-39	126	5.22	6.38	(0.134, 0.101)	67	
	F	Example 1-40	130	5.11	6.52	(0.133, 0.101)	30
		Example 1-41	135	5.27	6.55	(0.134, 0.101)	28
		Example 1-42	138	5.68	6.40	(0.134, 0.101)	36
55		Example 1-43	142	5.88	6.34	(0.134, 0.101)	37
		Example 1-44	144	4.53	7.21	(0.134, 0.104)	43
	Example 1-45	147	4.18	7.13	(0.134, 0.104)	45	
	Example 1-46	149	4.27	7.30	(0.134, 0.105)	39	
	Example 1-47	152	4.21	6.98	(0.134, 0.103)	41	
60	Example 1-48	155	4.97	6.56	(0.134, 0.101)	37	
	Example 1-49	161	4.57	7.00	(0.134, 0.101)	44	
	Example 1-50	164	5.12	6.48	(0.133, 0.102)	34	
	Example 1-51	168	4.32	7.11	(0.134, 0.100)	42	
	Example 1-52	172	5.11	6.42	(0.133, 0.101)	30	
	Example 1-53	174	5.27	6.55	(0.134, 0.101)	28	
	Example 1-54	178	5.68	6.42	(0.134, 0.101)	32	
	Example 1-55	181	5.88	6.30	(0.134, 0.101)	30	
	65	Example 1-56	186	5.14	6.51	(0.133, 0.101)	28
		Example 1-57	190	5.89	6.18	(0.133, 0.102)	80

501

TABLE 9-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 1-58	194	5.90	6.11	(0.134, 0.100)	78
Example 1-59	198	5.28	6.78	(0.133, 0.101)	27
Example 1-60	201	5.44	6.37	(0.134, 0.101)	26
Example 1-61	202	5.68	6.32	(0.133, 0.100)	37
Example 1-62	206	5.40	6.48	(0.134, 0.100)	25
Example 1-63	210	5.38	6.50	(0.133, 0.101)	28
Example 1-64	214	5.33	6.48	(0.134, 0.101)	28
Example 1-65	218	5.36	6.54	(0.134, 0.099)	27
Example 1-66	221	5.34	6.55	(0.134, 0.101)	30
Example 1-67	222	5.68	6.43	(0.133, 0.101)	31
Example 1-68	226	5.44	6.40	(0.134, 0.102)	33
Example 1-69	230	5.67	6.39	(0.134, 0.101)	35
Example 1-70	234	4.87	5.99	(0.132, 0.101)	29
Example 1-71	238	5.68	6.47	(0.134, 0.103)	31
Example 1-72	241	5.68	6.50	(0.134, 0.101)	34
Example 1-73	242	5.66	6.77	(0.133, 0.102)	29
Example 1-74	246	5.64	6.40	(0.134, 0.100)	32
Example 1-75	250	5.71	6.52	(0.134, 0.101)	33
Example 1-76	254	5.68	6.55	(0.133, 0.100)	30
Example 1-77	258	5.70	6.40	(0.133, 0.101)	30
Example 1-78	261	5.23	6.33	(0.133, 0.101)	31
Example 1-79	262	5.78	6.44	(0.133, 0.101)	37
Example 1-80	266	5.73	6.62	(0.133, 0.099)	31
Example 1-81	270	5.22	6.38	(0.134, 0.101)	67
Example 1-82	274	5.11	6.52	(0.133, 0.101)	30
Example 1-83	278	5.27	6.55	(0.134, 0.101)	28
Example 1-84	280	5.68	6.40	(0.134, 0.101)	36
Example 1-85	282	5.88	6.34	(0.134, 0.101)	37
Example 1-86	286	4.53	7.21	(0.134, 0.104)	43
Example 1-87	290	4.18	7.13	(0.134, 0.104)	45
Example 1-88	294	4.27	7.30	(0.134, 0.105)	39
Example 1-89	298	5.68	6.43	(0.133, 0.101)	31
Example 1-90	301	5.44	6.40	(0.134, 0.102)	33
Example 1-91	302	5.67	6.39	(0.134, 0.101)	35
Example 1-92	306	4.87	5.99	(0.132, 0.101)	29
Example 1-93	310	5.68	6.47	(0.134, 0.103)	31
Example 1-94	314	5.68	6.50	(0.134, 0.101)	34
Example 1-95	318	5.66	6.77	(0.133, 0.102)	29
Example 1-96	321	5.64	6.40	(0.134, 0.100)	32
Example 1-97	322	5.71	6.52	(0.134, 0.101)	33
Example 1-98	326	5.68	6.55	(0.133, 0.100)	30
Example 1-99	330	5.70	6.40	(0.133, 0.101)	30
Example 1-100	334	5.23	6.33	(0.133, 0.101)	31
Example 1-101	338	5.78	6.44	(0.133, 0.101)	37
Example 1-102	341	5.73	6.62	(0.133, 0.099)	31
Example 1-103	342	5.22	6.38	(0.134, 0.101)	67
Example 1-104	346	5.73	6.62	(0.133, 0.099)	31
Example 1-105	350	5.22	6.38	(0.134, 0.101)	67
Example 1-106	354	5.11	6.52	(0.133, 0.101)	30
Example 1-107	358	5.27	6.55	(0.134, 0.101)	28
Example 1-108	361	5.68	6.40	(0.134, 0.101)	36
Example 1-109	362	5.88	6.34	(0.134, 0.101)	37
Example 1-110	366	4.53	7.21	(0.134, 0.104)	43
Example 1-111	370	4.18	7.13	(0.134, 0.104)	45
Example 1-112	374	4.27	7.30	(0.134, 0.105)	39
Example 1-113	378	4.21	6.98	(0.134, 0.103)	41
Example 1-114	381	4.97	6.56	(0.134, 0.101)	37
Example 1-115	382	4.57	7.00	(0.134, 0.101)	44
Example 1-116	386	5.12	6.48	(0.133, 0.102)	34
Example 1-117	390	4.32	7.11	(0.134, 0.100)	42
Example 1-118	394	5.68	6.42	(0.134, 0.101)	32
Example 1-119	398	5.88	6.30	(0.134, 0.101)	30
Example 1-120	401	5.14	6.51	(0.133, 0.101)	28
Example 1-121	402	5.89	6.18	(0.133, 0.102)	80
Example 1-122	406	5.90	6.11	(0.134, 0.100)	78
Example 1-123	410	5.28	6.78	(0.133, 0.101)	27
Example 1-124	414	5.44	6.37	(0.134, 0.101)	26
Example 1-125	418	5.68	6.32	(0.133, 0.100)	37
Example 1-126	421	5.40	6.48	(0.134, 0.100)	25
Example 1-127	422	5.38	6.50	(0.133, 0.101)	28
Example 1-128	426	5.33	6.48	(0.134, 0.101)	28
Example 1-129	430	5.36	6.54	(0.134, 0.099)	27
Example 1-130	446	5.34	6.55	(0.134, 0.101)	30
Example 1-131	450	5.68	6.43	(0.133, 0.101)	31
Example 1-132	454	5.44	6.40	(0.134, 0.102)	33

502

TABLE 9-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 1-133	458	5.67	6.39	(0.134, 0.101)	35
Example 1-134	462	4.87	5.99	(0.132, 0.101)	29
Example 1-135	466	5.68	6.47	(0.134, 0.103)	31
Example 1-136	470	5.68	6.50	(0.134, 0.101)	34
Example 1-137	474	5.66	6.77	(0.133, 0.102)	29
Example 1-138	478	5.73	6.41	(0.133, 0.101)	54
Example 1-139	482	5.64	6.40	(0.134, 0.100)	32
Example 1-140	486	5.71	6.52	(0.134, 0.101)	33
Example 1-141	490	5.68	6.55	(0.133, 0.100)	30
Example 1-142	494	5.70	6.40	(0.133, 0.101)	30
Example 1-143	498	5.23	6.33	(0.133, 0.101)	31
Example 1-144	502	5.78	6.44	(0.133, 0.101)	37
Example 1-145	506	5.73	6.62	(0.133, 0.099)	31
Example 1-146	510	5.22	6.38	(0.134, 0.101)	67
Example 1-147	514	5.11	6.52	(0.133, 0.101)	30
Example 1-148	518	5.27	6.55	(0.134, 0.101)	28
Example 1-149	522	5.68	6.40	(0.134, 0.101)	36
Example 1-150	526	5.88	6.34	(0.134, 0.101)	37
Example 1-151	530	4.53	7.21	(0.134, 0.104)	43
Example 1-152	534	4.18	7.13	(0.134, 0.104)	45
Example 1-153	538	4.27	7.30	(0.134, 0.105)	39
Example 1-154	542	4.21	6.98	(0.134, 0.103)	41
Example 1-155	546	4.97	6.56	(0.134, 0.101)	37
Example 1-156	550	4.57	7.00	(0.134, 0.101)	44
Example 1-157	554	5.12	6.48	(0.133, 0.102)	34
Example 1-158	558	4.32	7.11	(0.134, 0.100)	42
Example 1-159	562	5.11	6.42	(0.133, 0.101)	30
Example 1-160	566	5.27	6.55	(0.134, 0.101)	28
Example 1-161	570	5.68	6.42	(0.134, 0.101)	32
Example 1-162	574	5.73	6.62	(0.133, 0.099)	31
Example 1-163	578	5.22	6.38	(0.134, 0.101)	67
Example 1-164	582	5.73	6.62	(0.133, 0.099)	31
Example 1-165	586	5.22	6.38	(0.134, 0.101)	67
Example 1-166	590	5.11	6.52	(0.133, 0.101)	30
Example 1-167	594	5.27	6.55	(0.134, 0.101)	28
Example 1-168	598	5.68	6.40	(0.134, 0.101)	36
Example 1-169	602	5.88	6.34	(0.134, 0.101)	37
Example 1-170	606	4.53	7.21	(0.134, 0.104)	43
Example 1-171	610	5.89	6.18	(0.133, 0.102)	80
Example 1-172	614	5.90	6.11	(0.134, 0.100)	78
Example 1-173	618	5.28	6.78	(0.133, 0.101)	27
Example 1-174	622	5.44	6.37	(0.134, 0.101)	26
Example 1-175	626	5.68	6.32	(0.133, 0.100)	37
Example 1-176	630	5.40	6.48	(0.134, 0.100)	25
Example 1-177	634	5.38	6.50	(0.133, 0.101)	28
Example 1-178	638	5.33	6.48	(0.134, 0.101)	28
Example 1-179	642	5.36	6.54	(0.134, 0.099)	27
Example 1-180	646	5.34	6.55	(0.134, 0.101)	30
Example 1-181	650	5.68	6.43	(0.133, 0.101)	31
Example 1-182	654	5.44	6.40	(0.134, 0.102)	33
Example 1-183	658	5.67	6.39	(0.134, 0.101)	35
Example 1-184	662	4.87	5.99	(0.132, 0.101)	29
Example 1-185	666	5.68	6.47	(0.134, 0.103)	31
Example 1-186	670	5.68	6.50	(0.134, 0.101)	34
Example 1-187	674	5.66	6.77	(0.133, 0.102)	29
Example 1-188	678	5.73	6.41	(0.133, 0.101)	54
Example 1-189	682	5.64	6.40	(0.134, 0.100)	32
Example 1-190	686	5.71	6.52	(0.134, 0.101)	33
Example 1-191	690	5.68	6.55	(0.133, 0.100)	30
Example 1-192	694	5.70	6.40	(0.133, 0.101)	30
Example 1-193	698	5.23	6.33	(0.133, 0.101)	31
Example 1-194	702	5.78	6.44	(0.133, 0.101)	37
Example 1-195	706	5.73	6.62	(0.133, 0.099)	31
Example 1-196	710	5.22	6.38	(0.134, 0.101)	67
Example 1-197	714	5.11	6.52	(0.133, 0.101)	30
Example 1-198	718	5.27	6.55	(0.134, 0.101)	28
Example 1-199	722	5.68	6.40	(0.134, 0.101)	36
Example 1-200	726	5.88	6.34	(0.134, 0.101)	37
Example 1-201	730	4.53	7.21	(0.134, 0.104)	43
Example 1-202	734	4.18	7.13	(0.134, 0.104)	45
Example 1-203	738	4.27	7.30	(0.134, 0.105)	39
Example 1-204	742	4.21	6.98	(0.134, 0.103)	41
Example 1-205	746	4.97	6.56	(0.134, 0.101)	37
Example 1-206	750	4.57	7.00	(0.134, 0.101)	44
Example 1-207	754	5.12	6.48	(0.133, 0.102)	34

503

TABLE 9-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 1-208	758	4.32	7.11	(0.134, 0.100)	42
Example 1-209	762	5.11	6.42	(0.133, 0.101)	30
Example 1-210	766	5.27	6.55	(0.134, 0.101)	28
Example 1-211	770	5.68	6.42	(0.134, 0.101)	32
Example 1-212	774	4.57	7.00	(0.134, 0.101)	44
Example 1-213	778	5.68	6.47	(0.134, 0.103)	31
Example 1-214	782	5.68	6.50	(0.134, 0.101)	34
Example 1-215	786	5.66	6.77	(0.133, 0.102)	29
Example 1-216	790	5.73	6.41	(0.133, 0.101)	54
Example 1-217	794	5.64	6.40	(0.134, 0.100)	32
Example 1-218	898	5.71	6.52	(0.134, 0.101)	33
Example 1-219	802	5.68	6.55	(0.133, 0.100)	30
Example 1-220	806	5.70	6.40	(0.133, 0.101)	30
Example 1-221	810	5.23	6.33	(0.133, 0.101)	31
Example 1-222	814	5.78	6.44	(0.133, 0.101)	37
Example 1-223	818	5.73	6.62	(0.133, 0.099)	31
Example 1-224	822	5.70	6.40	(0.133, 0.101)	30
Example 1-225	826	5.88	6.34	(0.134, 0.101)	37
Example 1-226	830	4.27	7.30	(0.134, 0.105)	39
Comparative Example 1-1	A	5.82	2.23	(0.134, 0.110)	27
Comparative Example 1-2	B	5.80	3.32	(0.134, 0.111)	29
Comparative Example 1-3	C	5.84	2.39	(0.134, 0.111)	25
Comparative Example 1-4	D	8.60	1.23	(0.134, 0.100)	21
Comparative Example 1-5	E	7.81	3.23	(0.128, 0.111)	10
Comparative Example 1-6	F	6.87	2.30	(0.125, 0.097)	12

As seen from the results of Table 9, the organic light emitting device using the charge generation layer material of the white organic light emitting device of the present disclosure had lower driving voltage and improved light emission efficiency compared to Comparative Examples 1-1 to 1-6.

Such a result is considered to be due to the fact that the compound of the present disclosure used as an N-type charge generation layer formed with the disclosed skeleton having proper length and strength, and flatness and a proper hetero-compound capable of binding to metals forms a gap state in the N-type charge generation layer by doping an alkali metal or an alkaline earth metal thereto, and electrons produced from a P-type charge generation layer are readily injected into an electron transfer layer through the gap state produced in the N-type charge generation layer. Accordingly, the P-type charge generation layer may favorably inject and transfer electrons to the N-type charge generation layer, and as a result, driving voltage was lowered, and efficiency and lifetime were improved in the organic light emitting device.

Experimental Example 2

1) Manufacture of Organic Light Emitting Device

A glass substrate on which indium tin oxide (ITO) was coated as a thin film to a thickness of 1,500 Å was cleaned


504

with distilled water ultrasonic waves. After the cleaning with distilled water was finished, the substrate was ultrasonic cleaned with solvents such as acetone, methanol and isopropyl alcohol, then dried, and UVO treatment was conducted for 5 minutes using UV in a UV cleaner. After that, the substrate was transferred to a plasma cleaner (PT), and after conducting plasma treatment under vacuum for ITO work function and residual film removal, the substrate was transferred to a thermal deposition apparatus for organic deposition.

On the transparent ITO electrode (anode), organic materials were formed in a 2-stack white organic light emitting device (WOLED) structure. As for the first stack, TAPC was thermal vacuum deposited first to a thickness of 300 Å to form a hole transfer layer. After forming the hole transfer layer, a light emitting layer was thermal vacuum deposited thereon as follows. As the light emitting layer, TCz1, a host, was 8% doped with Irpic, a blue phosphorescent dopant, and deposited to 300 Å. After forming an electron transfer layer to 400 Å using TmPyPB, a compound described in the following Table 10 was 20% doped with Cs₂CO₃ and formed to 100 Å as a charge generation layer.

As for the second stack, MoO₃ was thermal vacuum deposited first to a thickness of 50 Å to form a hole injection layer. A hole transfer layer, a common layer, was formed to 100 Å by 20% doping MoO₃ to TAPC, and then depositing the TAPC to 300 Å. A light emitting layer was formed thereon by 8% doping Ir(ppy)₃, a green phosphorescent dopant, to TCz1, a host, and depositing the result to 300 Å, and then an electron transfer layer was formed to 600 Å using TmPyPB. Lastly, an electron injection layer was formed on the electron transfer layer by depositing lithium fluoride (LiF) to a thickness of 10 Å, and then a cathode was formed on the electron injection layer by depositing an aluminum (Al) cathode to a thickness of 1,200 Å, and as a result, an organic light emitting device was manufactured.


Meanwhile, all the organic compounds required to manufacture the OLED were vacuum sublimation purified under 10⁻⁸ torr to 10⁻⁶ torr for each material to be used in the OLED manufacture.




TAPC

505



-continued



TCz1



Flpic


Ir(ppy)₃

TmPyPB

506

-continued

5



10

15

20

25

30

35

40

45

50

55

60

65

A

B


C

D

E

507

-continued



2) Driving Voltage and Light Emission Efficiency of Organic Light Emitting Device

For each of the organic light emitting devices manufactured as above, electroluminescent (EL) properties were measured using M7000 manufactured by McScience Inc., and with the measurement results, T_{95} was measured when standard luminance was 3,500 cd/m² through a lifetime measurement system (M6000) manufactured by McScience Inc. Results of measuring driving voltage, light emission efficiency, external quantum efficiency and color coordinate (CIE) of the white organic light emitting devices manufactured according to the present disclosure are as shown in the following Table 10.

TABLE 10

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T_{95})
Example 2-1	1	7.23	68.95	(0.218, 0.427)	35
Example 2-2	4	7.02	69.45	(0.220, 0.431)	49
Example 2-3	8	7.07	64.88	(0.200, 0.421)	32
Example 2-4	12	7.11	67.23	(0.205, 0.411)	40
Example 2-5	15	7.65	63.21	(0.221, 0.434)	33
Example 2-6	18	7.01	69.82	(0.220, 0.440)	43
Example 2-7	21	7.67	58.98	(0.219, 0.411)	35
Example 2-8	25	7.10	69.45	(0.219, 0.429)	40
Example 2-9	28	7.66	59.22	(0.215, 0.411)	30
Example 2-10	32	7.77	60.94	(0.211, 0.419)	32
Example 2-11	35	8.24	58.26	(0.209, 0.419)	31
Example 2-12	38	8.01	59.11	(0.207, 0.409)	33
Example 2-13	41	7.40	63.66	(0.208, 0.415)	29
Example 2-14	44	8.06	58.03	(0.208, 0.412)	52
Example 2-15	47	8.24	57.98	(0.208, 0.411)	56
Example 2-16	50	7.96	60.77	(0.208, 0.412)	27
Example 2-17	53	7.88	61.29	(0.209, 0.412)	30
Example 2-18	58	8.13	59.01	(0.207, 0.411)	49
Example 2-19	61	8.00	59.13	(0.231, 0.440)	34
Example 2-20	63	7.82	63.22	(0.232, 0.422)	26
Example 2-21	67	7.99	63.88	(0.230, 0.420)	30
Example 2-22	73	8.25	61.12	(0.223, 0.433)	36
Example 2-23	76	7.76	63.47	(0.222, 0.435)	31
Example 2-24	78	8.22	60.84	(0.218, 0.421)	30
Example 2-25	81	8.37	59.91	(0.220, 0.421)	30
Example 2-26	83	8.25	62.56	(0.224, 0.429)	32
Example 2-27	86	7.55	60.99	(0.215, 0.422)	27
Example 2-28	90	8.33	61.11	(0.214, 0.420)	33
Example 2-29	92	7.74	63.32	(0.230, 0.439)	37
Example 2-30	95	7.71	65.97	(0.208, 0.412)	29
Example 2-31	101	8.52	57.04	(0.231, 0.418)	70
Example 2-32	103	7.78	60.01	(0.208, 0.412)	32
Example 2-33	107	8.01	59.97	(0.209, 0.411)	41
Example 2-34	110	7.71	64.37	(0.208, 0.412)	30
Example 2-35	113	7.82	54.67	(0.233, 0.419)	30
Example 2-36	115	7.54	63.58	(0.208, 0.412)	31
Example 2-37	122	7.88	59.36	(0.207, 0.417)	37

508

TABLE 10-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T_{95})
Example 2-38	124	7.71	62.03	(0.220, 0.412)	29
Example 2-39	126	8.38	59.80	(0.231, 0.423)	71
Example 2-40	130	7.91	60.22	(0.215, 0.411)	28
Example 2-41	135	7.97	60.94	(0.211, 0.419)	31
Example 2-42	138	8.24	58.26	(0.209, 0.419)	35
Example 2-43	142	8.01	59.11	(0.207, 0.409)	37
Example 2-44	144	7.23	68.95	(0.218, 0.427)	35
Example 2-45	147	7.02	69.45	(0.220, 0.431)	49
Example 2-46	149	7.07	64.88	(0.200, 0.421)	32
Example 2-47	152	7.11	67.23	(0.205, 0.411)	40
Example 2-48	155	7.65	63.21	(0.221, 0.434)	33
Example 2-49	161	7.01	69.82	(0.220, 0.440)	43
Example 2-50	164	7.67	58.98	(0.219, 0.411)	35
Example 2-51	168	7.10	69.45	(0.219, 0.429)	40
Example 2-52	172	7.66	59.22	(0.215, 0.411)	30
Example 2-53	174	7.77	60.94	(0.211, 0.419)	32
Example 2-54	178	8.24	58.26	(0.209, 0.419)	31
Example 2-55	181	8.01	59.11	(0.207, 0.409)	33
Example 2-56	186	7.40	63.66	(0.208, 0.415)	29
Example 2-57	190	8.06	58.03	(0.208, 0.412)	52
Example 2-58	194	8.24	57.98	(0.208, 0.411)	56
Example 2-59	198	7.96	60.77	(0.208, 0.412)	27
Example 2-60	201	7.88	61.29	(0.209, 0.412)	30
Example 2-61	202	8.13	59.01	(0.207, 0.411)	49
Example 2-62	206	8.00	59.13	(0.231, 0.440)	34
Example 2-63	210	7.82	63.22	(0.232, 0.422)	26
Example 2-64	214	7.40	63.66	(0.208, 0.415)	29
Example 2-65	218	8.06	58.03	(0.208, 0.412)	52
Example 2-66	221	8.24	57.98	(0.208, 0.411)	56
Example 2-67	222	7.96	60.77	(0.208, 0.412)	27
Example 2-68	226	7.88	61.29	(0.209, 0.412)	30
Example 2-69	230	8.13	59.01	(0.207, 0.411)	49
Example 2-70	234	8.00	59.13	(0.231, 0.440)	34
Example 2-71	238	7.82	63.22	(0.232, 0.422)	26
Example 2-72	241	7.99	63.88	(0.230, 0.420)	30
Example 2-73	242	8.25	61.12	(0.223, 0.433)	36
Example 2-74	246	7.76	63.47	(0.222, 0.435)	31
Example 2-75	250	8.22	60.84	(0.218, 0.421)	30
Example 2-76	254	8.37	59.91	(0.220, 0.421)	30
Example 2-77	258	8.25	62.56	(0.224, 0.429)	32
Example 2-78	261	7.55	60.99	(0.215, 0.422)	27
Example 2-79	262	7.66	59.22	(0.215, 0.411)	30
Example 2-80	266	7.77	60.94	(0.211, 0.419)	32
Example 2-81	270	8.24	58.26	(0.209, 0.419)	31
Example 2-82	274	8.01	59.11	(0.207, 0.409)	33
Example 2-83	278	7.40	63.66	(0.208, 0.415)	29
Example 2-84	280	8.06	58.03	(0.208, 0.412)	52
Example 2-85	282	8.24	57.98	(0.208, 0.411)	56
Example 2-86	286	7.96	60.77	(0.208, 0.412)	27
Example 2-87	290	7.88	61.29	(0.209, 0.412)	30
Example 2-88	294	8.13	59.01	(0.207, 0.411)	49
Example 2-89	298	8.00	59.13	(0.231, 0.440)	34
Example 2-90	301	7.82	63.22	(0.232, 0.422)	26
Example 2-91	302	7.40	63.66	(0.208, 0.415)	29
Example 2-92	306	7.74	63.32	(0.230, 0.439)	37
Example 2-93	310	7.71	65.97	(0.208, 0.412)	29
Example 2-94	314	8.52	57.04	(0.231, 0.418)	70
Example 2-95	318	7.78	60.01	(0.208, 0.412)	32
Example 2-96	321	8.01	59.97	(0.209, 0.411)	41
Example 2-97	322	7.71	64.37	(0.208, 0.412)	30
Example 2-98	326	7.82	54.67	(0.233, 0.419)	30
Example 2-99	330	7.54	63.58	(0.208, 0.412)	31
Example 2-100	334	7.88	59.36	(0.207, 0.417)	37
Example 2-101	338	7.71	62.03	(0.220, 0.412)	29
Example 2-102	341	8.38	59.80	(0.231, 0.423)	71
Example 2-103	342	7.91	60.22	(0.215, 0.411)	28
Example 2-104	346	7.97	60.94	(0.211, 0.419)	31
Example 2-105	350	8.24	58.26	(0.209, 0.419)	35
Example 2-106	354	7.88	61.29	(0.209, 0.412)	30
Example 2-107	358	8.13	59.01	(0.207, 0.411)	49
Example 2-108	361	8.00	59.13	(0.231, 0.440)	34
Example 2-109	362	7.82	63.22	(0.232, 0.422)	26
Example 2-110	366	7.40	63.66	(0.208, 0.415)	29
Example 2-111	370	7.74	63.32	(0.230, 0.439)	37
Example 2-112	374	7.71	65.97	(0.208, 0.412)	29

509

TABLE 10-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 2-113	378	8.52	57.04	(0.231, 0.418)	70
Example 2-114	381	7.78	60.01	(0.208, 0.412)	32
Example 2-115	382	8.01	59.97	(0.209, 0.411)	41
Example 2-116	386	7.71	64.37	(0.208, 0.412)	30
Example 2-117	390	7.82	54.67	(0.233, 0.419)	30
Example 2-118	394	7.54	63.58	(0.208, 0.412)	31
Example 2-119	398	7.11	67.23	(0.205, 0.411)	40
Example 2-120	401	7.65	63.21	(0.221, 0.434)	33
Example 2-121	402	7.01	69.82	(0.220, 0.440)	43
Example 2-122	406	7.67	58.98	(0.219, 0.411)	35
Example 2-123	410	7.10	69.45	(0.219, 0.429)	40
Example 2-124	414	7.66	59.22	(0.215, 0.411)	30
Example 2-125	418	7.77	60.94	(0.211, 0.419)	32
Example 2-126	421	8.24	58.26	(0.209, 0.419)	31
Example 2-127	422	8.01	59.11	(0.207, 0.409)	33
Example 2-128	426	7.40	63.66	(0.208, 0.415)	29
Example 2-129	430	8.06	58.03	(0.208, 0.412)	52
Example 2-130	446	8.24	57.98	(0.208, 0.411)	56
Example 2-131	450	7.96	60.77	(0.208, 0.412)	27
Example 2-132	454	7.88	61.29	(0.209, 0.412)	30
Example 2-133	458	8.13	59.01	(0.207, 0.411)	49
Example 2-134	462	8.00	59.13	(0.231, 0.440)	34
Example 2-135	466	7.82	63.22	(0.232, 0.422)	26
Example 2-136	470	7.78	60.01	(0.208, 0.412)	32
Example 2-137	474	8.01	59.97	(0.209, 0.411)	41
Example 2-138	478	7.71	64.37	(0.208, 0.412)	30
Example 2-139	482	7.82	54.67	(0.233, 0.419)	30
Example 2-140	486	7.54	63.58	(0.208, 0.412)	31
Example 2-141	490	7.11	67.23	(0.205, 0.411)	40
Example 2-142	494	7.65	63.21	(0.221, 0.434)	33
Example 2-143	498	7.01	69.82	(0.220, 0.440)	43
Example 2-144	502	7.67	58.98	(0.219, 0.411)	35
Example 2-145	506	7.10	69.45	(0.219, 0.429)	40
Example 2-146	510	7.66	59.22	(0.215, 0.411)	30
Example 2-147	514	7.77	60.94	(0.211, 0.419)	32
Example 2-148	518	8.24	58.26	(0.209, 0.419)	31
Example 2-149	522	8.01	59.11	(0.207, 0.409)	33
Example 2-150	526	7.55	60.99	(0.215, 0.422)	27
Example 2-151	530	7.66	59.22	(0.215, 0.411)	30
Example 2-152	534	7.77	60.94	(0.211, 0.419)	32
Example 2-153	538	8.24	58.26	(0.209, 0.419)	31
Example 2-154	542	8.01	59.11	(0.207, 0.409)	33
Example 2-155	546	7.40	63.66	(0.208, 0.415)	29
Example 2-156	550	8.06	58.03	(0.208, 0.412)	52
Example 2-157	554	8.24	57.98	(0.208, 0.411)	56
Example 2-158	558	7.96	60.77	(0.208, 0.412)	27
Example 2-159	562	7.88	61.29	(0.209, 0.412)	30
Example 2-160	566	8.13	59.01	(0.207, 0.411)	49
Example 2-161	570	8.00	59.13	(0.231, 0.440)	34
Example 2-162	574	7.82	63.22	(0.232, 0.422)	26
Example 2-163	578	7.40	63.66	(0.208, 0.415)	29
Example 2-164	582	7.74	63.32	(0.230, 0.439)	37
Example 2-165	586	7.71	65.97	(0.208, 0.412)	29
Example 2-166	590	8.52	57.04	(0.231, 0.418)	70
Example 2-167	594	7.78	60.01	(0.208, 0.412)	32
Example 2-168	598	8.01	59.97	(0.209, 0.411)	41
Example 2-169	602	7.71	64.37	(0.208, 0.412)	30
Example 2-170	606	7.82	54.67	(0.233, 0.419)	30
Example 2-171	610	7.54	63.58	(0.208, 0.412)	31
Example 2-172	614	7.88	59.36	(0.207, 0.417)	37
Example 2-173	618	7.71	62.03	(0.220, 0.412)	29
Example 2-174	622	7.82	63.22	(0.232, 0.422)	26
Example 2-175	626	7.40	63.66	(0.208, 0.415)	29
Example 2-176	630	7.74	63.32	(0.230, 0.439)	37
Example 2-177	634	7.71	65.97	(0.208, 0.412)	29
Example 2-178	638	8.52	57.04	(0.231, 0.418)	70
Example 2-179	642	7.78	60.01	(0.208, 0.412)	32
Example 2-180	646	8.01	59.97	(0.209, 0.411)	41
Example 2-181	650	7.71	64.37	(0.208, 0.412)	30
Example 2-182	654	7.82	54.67	(0.233, 0.419)	30
Example 2-183	658	7.54	63.58	(0.208, 0.412)	31
Example 2-184	662	7.88	59.36	(0.207, 0.417)	37
Example 2-185	666	7.71	62.03	(0.220, 0.412)	29
Example 2-186	670	7.66	59.22	(0.215, 0.411)	30
Example 2-187	674	7.77	60.94	(0.211, 0.419)	32

510

TABLE 10-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 2-188	678	8.24	58.26	(0.209, 0.419)	31
Example 2-189	682	8.01	59.11	(0.207, 0.409)	33
Example 2-190	686	7.55	60.99	(0.215, 0.422)	27
Example 2-191	690	7.66	59.22	(0.215, 0.411)	30
Example 2-192	694	7.77	60.94	(0.211, 0.419)	32
Example 2-193	698	7.45	71.80	(0.210, 0.418)	35
Example 2-194	702	7.11	67.23	(0.205, 0.411)	40
Example 2-195	706	7.65	63.21	(0.221, 0.434)	33
Example 2-196	710	7.01	69.82	(0.220, 0.440)	43
Example 2-197	714	7.67	58.98	(0.219, 0.411)	35
Example 2-198	718	7.10	69.45	(0.219, 0.429)	40
Example 2-199	722	7.66	59.22	(0.215, 0.411)	30
Example 2-200	726	7.77	60.94	(0.211, 0.419)	32
Example 2-201	730	8.24	58.26	(0.209, 0.419)	31
Example 2-202	734	8.01	59.11	(0.207, 0.409)	33
Example 2-203	738	7.40	63.66	(0.208, 0.415)	29
Example 2-204	742	8.06	58.03	(0.208, 0.412)	52
Example 2-205	746	8.24	57.98	(0.208, 0.411)	56
Example 2-206	750	7.96	60.77	(0.208, 0.412)	27
Example 2-207	754	7.88	61.29	(0.209, 0.412)	30
Example 2-208	758	8.13	59.01	(0.207, 0.411)	49
Example 2-209	762	8.00	59.13	(0.231, 0.440)	34
Example 2-210	766	7.82	63.22	(0.232, 0.422)	26
Example 2-211	770	7.66	59.22	(0.215, 0.411)	30
Example 2-212	774	7.77	60.94	(0.211, 0.419)	32
Example 2-213	778	8.24	58.26	(0.209, 0.419)	31
Example 2-214	782	8.01	59.11	(0.207, 0.409)	33
Example 2-215	786	7.40	63.66	(0.208, 0.415)	29
Example 2-216	790	8.06	58.03	(0.208, 0.412)	52
Example 2-217	794	8.24	57.98	(0.208, 0.411)	56
Example 2-218	898	7.96	60.77	(0.208, 0.412)	27
Example 2-219	802	7.88	61.29	(0.209, 0.412)	30
Example 2-220	806	8.13	59.01	(0.207, 0.411)	49
Example 2-221	810	7.71	64.37	(0.208, 0.412)	30
Example 2-222	814	7.82	54.67	(0.233, 0.419)	30
Example 2-223	818	7.54	63.58	(0.208, 0.412)	31
Example 2-224	822	7.88	59.36	(0.207, 0.417)	37
Example 2-225	826	7.71	62.03	(0.220, 0.412)	29
Example 2-226	830	7.82	63.22	(0.232, 0.422)	26
Comparative	A	2.82	23.23	(0.134, 0.110)	21
Example 2-1					
Comparative	B	3.80	32.32	(0.134, 0.111)	19
Example 2-2					
Comparative	C	5.64	15.65	(0.128, 0.099)	8
Example 2-3					
Comparative	D	3.20	18.22	(0.119, 0.100)	11
Example 2-4					
Comparative	E	6.54	10.88	(0.128, 0.111)	9
Example 2-5					
Comparative	F	2.34	9.86	(0.125, 0.097)	15
Example 2-6					

50 As seen from the results of Table 10, the organic light emitting device using the charge generation layer material of the 2-stack white organic light emitting device of the present disclosure had improved light emission efficiency and life-time compared to Comparative Examples 2-1 to 2-6.

55 Such a result is considered to be due to the fact that the compound of the present disclosure used as an N-type charge generation layer formed with the disclosed skeleton having proper length and strength, and flatness and a proper hetero-compound capable of binding to metals forms a gap state in the N-type charge generation layer by doping an alkali metal or an alkaline earth metal thereto, and electrons produced from a P-type charge generation layer are readily injected into an electron transfer layer through the gap state produced in the N-type charge generation layer. Accord-
60 ingly, the P-type charge generation layer may favorably inject and transfer electrons to the N-type charge generation
65

511


layer, and as a result, driving voltage was lowered, and efficiency and lifetime were improved in the organic light emitting device.

Experimental Example 3

1) Manufacture of Organic Light Emitting Device

A transparent ITO electrode thin film obtained from glass for an OLED (manufactured by Samsung-Corning Co., Ltd.) was ultrasonic cleaned using trichloroethylene, acetone, ethanol and distilled water consecutively for 5 minutes each, stored in isopropanol, and used.


Next, the ITO substrate was installed in a substrate folder of a vacuum deposition apparatus, and the following 4,4', 4''-tris(N,N-(2-naphthyl)-phenylamino)triphenylamine (2-TNATA) was introduced to a cell in the vacuum deposition apparatus.



2-TNATA

Subsequently, the chamber was evacuated until the degree of vacuum therein reached 10^{-6} torr, and then 2-TNATA was evaporated by applying a current to the cell to deposit a hole injection layer having a thickness of 600 Å on the ITO substrate.


To another cell in the vacuum deposition apparatus, the following N,N'-bis(α -naphthyl)-N,N'-diphenyl-4,4'-diamine (NPB) was introduced, and evaporated by applying a current to the cell to deposit a hole transfer layer having a thickness of 300 Å on the hole injection layer.




NPB

512

After forming the hole injection layer and the hole transfer layer as above, a blue light emitting material having a structure as below was deposited thereon as a light emitting layer. Specifically, in one side cell in the vacuum deposition apparatus, H1, a blue light emitting host material, was vacuum deposited to a thickness of 200 Å, and D1, a blue light emitting dopant material, was vacuum deposited thereon by 5% with respect to the host material.




H1




D1

Subsequently, a compound of the following Table 11 was deposited to a thickness of 300 Å as an electron transfer layer.




A



B

513

-continued



C

2) Driving Voltage and Light Emission Efficiency of Organic Light Emitting Device

For each of the organic light emitting devices manufactured as above, electroluminescent (EL) properties were measured using M7000 manufactured by McScience Inc., and with the measurement results, T_{95} was measured when standard luminance was 700 cd/m^2 through a lifetime measurement system (M6000) manufactured by McScience Inc. Results of measuring driving voltage, light emission efficiency, external quantum efficiency and color coordinate (CIE) of the white organic light emitting devices manufactured according to the present disclosure are as shown in Table 11.

D 15

TABLE 11

				Light Emission Efficiency			
		Com- pound	Driving Voltage (V)	(cd/A)	CIE (x, y)	Life- time (T ₉₅)	
20							
		Example 3-1	1	5.50	6.32	(0.134, 0.101)	33
		Example 3-2	4	5.44	6.44	(0.134, 0.102)	32
		Example 3-3	8	5.34	6.38	(0.134, 0.101)	31
		Example 3-4	12	5.38	6.20	(0.134, 0.103)	35
		Example 3-5	15	5.60	6.12	(0.134, 0.102)	34
		Example 3-6	18	5.45	6.01	(0.134, 0.101)	33
		Example 3-7	21	5.44	6.22	(0.134, 0.102)	30
		Example 3-8	25	5.46	6.18	(0.134, 0.101)	29
		Example 3-9	28	5.40	6.13	(0.134, 0.101)	31
		Example 3-10	32	5.44	6.30	(0.134, 0.100)	32
		Example 3-11	35	5.37	6.35	(0.134, 0.101)	32
		Example 3-12	38	5.38	6.41	(0.134, 0.100)	30
		Example 3-13	41	4.81	6.93	(0.134, 0.100)	30
		Example 3-14	44	5.48	6.21	(0.134, 0.100)	87
		Example 3-15	47	5.47	6.28	(0.134, 0.100)	79
		Example 3-16	50	4.45	6.98	(0.134, 0.100)	42
		Example 3-17	53	4.52	6.63	(0.134, 0.102)	44
		Example 3-18	58	5.12	6.20	(0.134, 0.101)	40
		Example 3-19	61	4.39	6.87	(0.134, 0.102)	43
		Example 3-20	63	4.71	6.48	(0.134, 0.100)	34
		Example 3-21	67	4.38	7.00	(0.134, 0.103)	39
		Example 3-22	73	5.34	6.31	(0.134, 0.100)	36
		Example 3-23	76	5.40	6.36	(0.134, 0.102)	32
		Example 3-24	78	5.42	6.26	(0.134, 0.101)	32
		Example 3-25	81	5.39	6.19	(0.134, 0.100)	31
		Example 3-26	83	5.55	6.27	(0.134, 0.102)	31
		Example 3-27	86	4.98	6.20	(0.134, 0.103)	30
		Example 3-28	90	5.41	6.19	(0.134, 0.100)	32
		Example 3-29	92	5.22	6.28	(0.134, 0.103)	36
		Example 3-30	95	5.19	6.41	(0.134, 0.102)	33
		Example 3-31	101	5.43	6.17	(0.134, 0.100)	62
		Example 3-32	103	4.94	6.85	(0.134, 0.099)	40
		Example 3-33	107	4.51	6.97	(0.134, 0.102)	42
		Example 3-34	110	4.45	7.03	(0.134, 0.100)	39
		Example 3-35	113	5.00	6.21	(0.134, 0.103)	32
		Example 3-36	115	4.93	6.35	(0.134, 0.101)	35
		Example 3-37	122	4.50	6.92	(0.134, 0.104)	41
		Example 3-38	124	5.03	6.27	(0.134, 0.100)	35
		Example 3-39	126	5.11	6.22	(0.134, 0.103)	36
		Example 3-40	130	5.01	6.98	(0.134, 0.100)	31
		Example 3-41	135	4.98	7.10	(0.134, 0.103)	33
		Example 3-42	138	5.34	6.21	(0.134, 0.100)	36
		Example 3-43	142	5.40	6.36	(0.134, 0.102)	39
		Example 3-44	144	5.42	6.26	(0.134, 0.101)	32
		Example 3-45	147	5.39	6.19	(0.134, 0.100)	31
		Example 3-46	149	5.55	6.27	(0.134, 0.102)	31
		Example 3-47	152	4.98	6.20	(0.134, 0.103)	30
		Example 3-48	155	5.41	6.19	(0.134, 0.100)	32
		Example 3-49	161	5.22	6.28	(0.134, 0.103)	36
		Example 3-50	164	5.19	6.41	(0.134, 0.102)	33
		Example 3-51	168	5.43	6.17	(0.134, 0.100)	62
		Example 3-52	172	4.94	6.85	(0.134, 0.099)	40
		Example 3-53	174	4.51	6.97	(0.134, 0.102)	42
		Example 3-54	178	4.45	7.03	(0.134, 0.100)	39
		Example 3-55	181	5.00	6.21	(0.134, 0.103)	32
		Example 3-56	186	5.43	6.17	(0.134, 0.100)	62
		Example 3-57	190	4.94	6.85	(0.134, 0.099)	40

As an electron injection layer, lithium fluoride (LiF) was deposited to a thickness of 10 Å, and an Al cathode was employed to a thickness of 1,000 Å, and as a result, an OLED was manufactured.

Meanwhile, all the organic compounds required to manufacture the OLED were vacuum sublimation purified under 10^{-8} torr to 10^{-6} torr by each material to be used in the OLED manufacture.

515

TABLE 11-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 3-58	194	4.51	6.97	(0.134, 0.102)	42
Example 3-59	198	4.45	7.03	(0.134, 0.100)	39
Example 3-60	201	5.00	6.21	(0.134, 0.103)	32
Example 3-61	202	4.93	6.35	(0.134, 0.101)	35
Example 3-62	206	4.50	6.92	(0.134, 0.104)	41
Example 3-63	210	5.03	6.27	(0.134, 0.100)	35
Example 3-64	214	5.11	6.22	(0.134, 0.103)	36
Example 3-65	218	5.01	6.98	(0.134, 0.100)	31
Example 3-66	221	4.98	7.10	(0.134, 0.103)	33
Example 3-67	222	5.34	6.21	(0.134, 0.100)	36
Example 3-68	226	5.40	6.36	(0.134, 0.102)	39
Example 3-69	230	5.42	6.26	(0.134, 0.101)	32
Example 3-70	234	5.22	6.28	(0.134, 0.103)	36
Example 3-71	238	5.19	6.41	(0.134, 0.102)	33
Example 3-72	241	5.43	6.17	(0.134, 0.100)	62
Example 3-73	242	4.94	6.85	(0.134, 0.099)	40
Example 3-74	246	4.51	6.97	(0.134, 0.102)	42
Example 3-75	250	4.45	7.03	(0.134, 0.100)	39
Example 3-76	254	5.00	6.21	(0.134, 0.103)	32
Example 3-77	258	5.43	6.17	(0.134, 0.100)	62
Example 3-78	261	4.94	6.85	(0.134, 0.099)	40
Example 3-79	262	4.51	6.97	(0.134, 0.102)	42
Example 3-80	266	4.45	7.03	(0.134, 0.100)	39
Example 3-81	270	5.00	6.21	(0.134, 0.103)	32
Example 3-82	274	4.93	6.35	(0.134, 0.101)	35
Example 3-83	278	4.94	6.85	(0.134, 0.099)	40
Example 3-84	280	4.51	6.97	(0.134, 0.102)	42
Example 3-85	282	4.45	7.03	(0.134, 0.100)	39
Example 3-86	286	5.00	6.21	(0.134, 0.103)	32
Example 3-87	290	4.93	6.35	(0.134, 0.101)	35
Example 3-88	294	4.50	6.92	(0.134, 0.104)	41
Example 3-89	298	5.03	6.27	(0.134, 0.100)	35
Example 3-90	301	5.11	6.22	(0.134, 0.103)	36
Example 3-91	302	5.01	6.98	(0.134, 0.100)	31
Example 3-92	306	4.98	7.10	(0.134, 0.103)	33
Example 3-93	310	5.01	6.98	(0.134, 0.100)	31
Example 3-94	314	4.98	7.10	(0.134, 0.103)	33
Example 3-95	318	5.34	6.21	(0.134, 0.100)	36
Example 3-96	321	5.40	6.36	(0.134, 0.102)	39
Example 3-97	322	5.42	6.26	(0.134, 0.101)	32
Example 3-98	326	5.22	6.28	(0.134, 0.103)	36
Example 3-99	330	5.19	6.41	(0.134, 0.102)	33
Example 3-100	334	5.43	6.17	(0.134, 0.100)	62
Example 3-101	338	4.94	6.85	(0.134, 0.099)	40
Example 3-102	341	4.51	6.97	(0.134, 0.102)	42
Example 3-103	342	4.45	7.03	(0.134, 0.100)	39
Example 3-104	346	5.00	6.21	(0.134, 0.103)	32
Example 3-105	350	5.43	6.17	(0.134, 0.100)	62
Example 3-106	354	5.22	6.28	(0.134, 0.103)	36
Example 3-107	358	5.19	6.41	(0.134, 0.102)	33
Example 3-108	361	5.43	6.17	(0.134, 0.100)	62
Example 3-109	362	4.94	6.85	(0.134, 0.099)	40
Example 3-110	366	4.51	6.97	(0.134, 0.102)	42
Example 3-111	370	4.45	7.03	(0.134, 0.100)	39
Example 3-112	374	5.00	6.21	(0.134, 0.103)	32
Example 3-113	378	5.43	6.17	(0.134, 0.100)	62
Example 3-114	381	4.94	6.85	(0.134, 0.099)	40
Example 3-115	382	4.51	6.97	(0.134, 0.102)	42
Example 3-116	386	4.45	7.03	(0.134, 0.100)	39
Example 3-117	390	5.00	6.21	(0.134, 0.103)	32
Example 3-118	394	4.93	6.35	(0.134, 0.101)	35
Example 3-119	398	4.50	6.92	(0.134, 0.104)	41
Example 3-120	401	5.03	6.27	(0.134, 0.100)	35
Example 3-121	402	5.48	6.21	(0.134, 0.100)	87
Example 3-122	406	5.47	6.28	(0.134, 0.100)	79
Example 3-123	410	4.45	6.98	(0.134, 0.100)	42
Example 3-124	414	4.52	6.63	(0.134, 0.102)	44
Example 3-125	418	5.12	6.20	(0.134, 0.101)	40
Example 3-126	421	4.39	6.87	(0.134, 0.102)	43
Example 3-127	422	4.71	6.48	(0.134, 0.100)	34
Example 3-128	426	4.38	7.00	(0.134, 0.103)	39
Example 3-129	430	5.34	6.31	(0.134, 0.100)	36
Example 3-130	446	5.40	6.36	(0.134, 0.102)	32
Example 3-131	450	5.42	6.26	(0.134, 0.101)	32
Example 3-132	454	5.39	6.19	(0.134, 0.100)	31

516

TABLE 11-continued

	Com- pound	Driving Voltage (V)	Light Emission Efficiency (cd/A)	CIE (x, y)	Life- time (T ₉₅)
Example 3-133	458	5.55	6.27	(0.134, 0.102)	31
Example 3-134	462	4.98	6.20	(0.134, 0.103)	30
Example 3-135	466	5.41	6.19	(0.134, 0.100)	32
Example 3-136	470	5.22	6.28	(0.134, 0.103)	36
Example 3-137	474	5.19	6.41	(0.134, 0.102)	33
Example 3-138	478	5.43	6.17	(0.134, 0.100)	62
Example 3-139	482	4.94	6.85	(0.134, 0.099)	40
Example 3-140	486	4.51	6.97	(0.134, 0.102)	42
Example 3-141	490	4.45	7.03	(0.134, 0.100)	39
Example 3-142	494	5.00	6.21	(0.134, 0.103)	32
Example 3-143	498	4.93	6.35	(0.134, 0.101)	35
Example 3-144	502	4.50	6.92	(0.134, 0.104)	41
Example 3-145	506	5.03	6.27	(0.134, 0.100)	35
Example 3-146	510	5.11	6.22	(0.134, 0.103)	36
Example 3-147	514	5.01	6.98	(0.134, 0.100)	31
Example 3-148	518	4.98	7.10	(0.134, 0.103)	33
Example 3-149	522	5.34	6.21	(0.134, 0.100)	36
Example 3-150	526	5.40	6.36	(0.134, 0.102)	39
Example 3-151	530	5.42	6.26	(0.134, 0.101)	32
Example 3-152	534	5.39	6.19	(0.134, 0.100)	31
Example 3-153	538	5.55	6.27	(0.134, 0.102)	31
Example 3-154	542	4.98	6.20	(0.134, 0.103)	30
Example 3-155	546	5.41	6.19	(0.134, 0.100)	32
Example 3-156	550	5.22	6.28	(0.134, 0.103)	36
Example 3-157	554	5.19	6.41	(0.134, 0.102)	33
Example 3-158	558	5.43	6.17	(0.134, 0.100)	62
Example 3-159	562	4.94	6.85	(0.134, 0.099)	40
Example 3-160	566	4.51	6.97	(0.134, 0.102)	42
Example 3-161	570	4.45	7.03	(0.134, 0.100)	39
Example 3-162	574	5.00	6.21	(0.134, 0.103)	32
Example 3-163	578	5.43	6.17	(0.134, 0.100)	62
Example 3-164	582	4.94	6.85	(0.134, 0.099)	40
Example 3-165	586	5.43	6.17	(0.134, 0.100)	62
Example 3-166	590	4.94	6.85	(0.134, 0.099)	40
Example 3-167	594	4.51	6.97	(0.134, 0.102)	42
Example 3-168	598	4.45	7.03	(0.134, 0.100)	39
Example 3-169	602	5.00	6.21	(0.134, 0.103)	32
Example 3-170	606	5.43	6.17	(0.134, 0.100)	62
Example 3-171	610	4.94	6.85	(0.134, 0.099)	40
Example 3-172	614	4.51	6.97	(0.134, 0.102)	42
Example 3-173	618	4.45	7.03	(0.134, 0.100)	39
Example 3-174	622	5.00	6.21	(0.134, 0.103)	32
Example 3-175	626	4.93	6.35	(0.134, 0.101)	35
Example 3-176	630	4.50	6.92	(0.134, 0.104)	41
Example 3-177	634	5.03	6.27	(0.134, 0.100)	35
Example 3-178	638	5.48	6.21	(0.134, 0.100)	87
Example 3-179	642	5.47	6.28	(0.134, 0.100)	79
Example 3-180	646	4.45	6.98	(0.134, 0.100)	42
Example 3-181	650	4.52	6.63	(0.134, 0.102)	44
Example 3-182	654	5.12	6.20	(0.134, 0.101)	40
Example 3-183	658	4.39	6.87	(0.134, 0.102)	43
Example 3-184	662	4.71	6.48	(0.134, 0.100)	34
Example 3-185	666	5.22	6.28	(0.134, 0.103)	36
Example 3-186	670	5.19	6.41	(0.134, 0.102)	33
Example 3-187	674	5.43	6.17	(0.134, 0.100)	62
Example 3-188	678	4.94	6.85	(0.134, 0.099)	40
Example 3-189	682	4.51	6.97	(0.134, 0.102)	42
Example 3-190	686	4.45	7.03	(0.134, 0.100)	39
Example 3-191	690	5.00	6.21	(0.134, 0.103)	32
Example 3-192	694	5.43	6.17	(0.134, 0.100)	62
Example 3-193	698	4.94	6.85	(0.134, 0.099)	40
Example 3-194	702	5.43	6.17	(0.134, 0.100)	62
Example 3-195	706	4.94	6.85	(0.134, 0.099)	40
Example 3-196	710	4.51	6.97	(0.134, 0.102)	42
Example 3-197	714	5.01	6.98	(0.134, 0.100)	31
Example 3-198	718	4.98	7.10	(0.134, 0.103)	33
Example 3-199	722	5.34	6.21	(0.134, 0.100)	36
Example 3-200	726	5.40	6.36	(0.134, 0.102)	39
Example 3-201	730	5.42	6.26	(0.134, 0.101)	32
Example 3-202	734	5.39	6.19	(0.134, 0.100)	31
Example 3-203	738	5.55	6.27	(0.134, 0.102)	31
Example 3-204	742	4.98	6.20	(0.134, 0.103)	30
Example 3-205	746	5.41	6.19	(0.134, 0.100)	32
Example 3-206	750	5.22	6.28	(0.134, 0.103)	36
Example 3-207	754	4.51	6.97	(0.134, 0.102)	42

517

TABLE 11-continued

	Com- pound	Driving Voltage (V)	Light		Life- time (T ₉₅)
			Emission Efficiency (cd/A)	CIE (x, y)	
Example 3-208	758	4.45	7.03	(0.134, 0.100)	39
Example 3-209	762	5.00	6.21	(0.134, 0.103)	32
Example 3-210	766	4.93	6.35	(0.134, 0.101)	35
Example 3-211	770	4.50	6.92	(0.134, 0.104)	41
Example 3-212	774	5.03	6.27	(0.134, 0.100)	35
Example 3-213	778	5.11	6.22	(0.134, 0.103)	36
Example 3-214	782	5.01	6.98	(0.134, 0.100)	31
Example 3-215	786	4.98	7.10	(0.134, 0.103)	33
Example 3-216	790	5.01	6.98	(0.134, 0.100)	31
Example 3-217	794	4.98	7.10	(0.134, 0.103)	33
Example 3-218	898	5.34	6.21	(0.134, 0.100)	36
Example 3-219	802	5.22	6.28	(0.134, 0.103)	36
Example 3-220	806	5.19	6.41	(0.134, 0.102)	33
Example 3-221	810	5.43	6.17	(0.134, 0.100)	62
Example 3-222	814	4.94	6.85	(0.134, 0.099)	40
Example 3-223	818	4.51	6.97	(0.134, 0.102)	42
Example 3-224	822	4.50	6.92	(0.134, 0.104)	41
Example 3-225	826	5.43	6.17	(0.134, 0.100)	62
Example 3-226	830	4.94	6.85	(0.134, 0.099)	40
Comparative Example 3-1	A	2.82	2.23	(0.134, 0.110)	15
Comparative Example 3-2	B	3.80	4.32	(0.134, 0.111)	20
Comparative Example 3-3	C	1.78	3.39	(0.128, 0.099)	11
Comparative Example 3-4	D	3.56	1.23	(0.119, 0.100)	9
Comparative Example 3-5	E	1.89	2.23	(0.128, 0.111)	10
Comparative Example 3-6	F	2.13	1.30	(0.125, 0.097)	11

As seen from the results of Table 11, the organic light emitting device using the electron transfer layer material of the white organic light emitting device of the present disclosure had significantly improved light emission efficiency and lifetime compared to Comparative Examples 3-1 to 3-6.


Such a result is considered to be due to the fact that, when using the disclosed compound having proper length and strength, and flatness as an electron transfer layer, a compound in an excited state is made by receiving electrons under a specific condition, and particularly when an excited state is formed in the hetero-skeleton site of the compound, excited energy moves to a stable state before the excited hetero-skeleton site goes through other reactions, and as a result, the relatively stabilized compound is capable of efficiently transferring electrons without the compound being decomposed or destroyed. For reference, those that are stable when excited are considered to be aryl or acene-based compounds or polycyclic hetero-compounds.

Accordingly, it is considered that the compound of the present disclosure brought excellence in all aspects of driving, efficiency and lifetime by enhancing improved electron-transfer properties or improved stability.

518

The invention claimed is:

1. A heterocyclic compound represented by the following Chemical Formula 1:



[Chemical Formula 1]

wherein, in Chemical Formula 1,

X is O or S,

L is a direct bond; a substituted or unsubstituted C6 to C30 arylene group; or a substituted or unsubstituted C2 to C30 heteroarylene group,

Z is a substituted or unsubstituted C6 to C30 aryl group; a substituted or unsubstituted C2 to C30 heteroaryl group or a substituted or unsubstituted phosphine oxide group,

R1 is a substituted or unsubstituted C6 to C30 aryl group; or a substituted or unsubstituted C2 to C30 heteroaryl group,


R2 to R5 are each independently hydrogen or deuterium, a is an integer of 1 to 4,

b is an integer of 1 to 3,

m and n are each an integer of 1 to 5, and

when a, b, m and n are each 2 or greater, substituents in the parentheses are the same as or different from each other.


2. The heterocyclic compound of claim 1, wherein Chemical Formula 1 is represented by the following Chemical Formula 2 or 3:



[Chemical Formula 2]

519

-continued




[Chemical Formula 3]


in Chemical Formulae 2 and 3,

L, Z, R1, R4, R5, a, b, m and n have the same definitions as in Chemical Formula 1.


3. The heterocyclic compound of claim 1, wherein Chemical Formula 1 is represented by any one of the following Chemical Formulae 4 to 6:



[Chemical Formula 4]



[Chemical Formula 5]



[Chemical Formula 6]

in Chemical Formulae 4 to 6,

X, L, Z, R1 to R5, a, b, m and n have the same definitions as in Chemical Formula 1.


520

4. The heterocyclic compound of claim 1, wherein R1 is a substituted or unsubstituted C6 to C30 aryl group.

5. The heterocyclic compound of claim 1, wherein L is a direct bond; a phenylene group; a biphenylene group; a terphenylene group; a naphthylene group; an anthracenylene group; a triphenylenylene group; or a phenanthrenylene group.


6. The heterocyclic compound of claim 1, wherein Z is a substituted or unsubstituted phenyl group; a biphenyl group; a terphenyl group; a naphthyl group; a triphenylenyl group; a phenanthrenyl group; an anthracenyl group; a dimethylfluorenyl group; a diphenylfluorenyl group; a spirobifluorenyl group; an isoquinolinyl group; a quinazolinyl group; a phenoxazinyl group; a phenothiazinyl group; an indolocarbazole group; a benzonaphthothiophene group; a substituted or unsubstituted pyrazole group; a substituted or unsubstituted pyridine group; a substituted or unsubstituted pyrimidine group; a substituted or unsubstituted triazine group; a substituted or unsubstituted carbazole group; a substituted or unsubstituted phenanthrolinyl group; a substituted or unsubstituted dibenzofuran group; a substituted or unsubstituted dibenzothiophene group; a substituted or unsubstituted dihydroacridine group; or a substituted or unsubstituted phosphine oxide group.

7. The heterocyclic compound of claim 1, wherein Chemical Formula 1 is represented by any one of the following compounds:




521

-continued




523

-continued


**524**

-continued



525

-continued



14

5

10

15

20

15

25

30

35

40

45



16

50


55

60


65

**526**


-continued



17




18



19

527

-continued




20

5

10

15

21 20




25

30

35

40

22 45



50


55

60


65

528


-continued



23






24



25

529

-continued

**530**

-continued

26

5

10

15

20

27

25

30

35

40

45

28

50

55




60

65

29


30

31



531

-continued



32

5

10

15

20


25

30

35

40


33



65

532

-continued



34


45

50

55



60

35



533

-continued

**534**

-continued

36

5

10

15

20

25

30

35

40

37



45

50

55

60

65






38




39

535

-continued


**536**

-continued



537

-continued



46

5

10


15

20

25

538

-continued



48

25

30

35

40

47


45

50

55



60

65






49

50






539

-continued




**540**

-continued



541

-continued

**542**

-continued

57

60

5

10

15

58 20

25

30

35

40

45





59

50




55

60

65




-continued




-continued

67



65


68



66




50

69



545

-continued

**546**

-continued

70

5

10

15

71

20

25

30

35

40

72

45

50

55




60

65

73




74

75



547


-continued

**548**

-continued


76

79




77 20

80



78 45




81



65

549

-continued

**550**

-continued

82

5

10

15

20

83

25

30

35

40

45

84


50

55


60

65


85



86






87



551


-continued

**552**

-continued

88

91



89


25

30

35

40

92



45

90

50




55

60




65

553

-continued




**554**

-continued



555

-continued

**556**

-continued

99

102

5

10

15

20

100

25

30

35

40

101




45

50

55


60

65




557

-continued


**558**

-continued



559

-continued



111

5

10

15

20

25

30

35

40

112


45

50


55

60

65


**560**

-continued





113

114






561

-continued




**562**

-continued



563

-continued

**564**

-continued

120

5

10

15

20

121 25

30

35

40

45


122 50

55


60

65


123



124





125



565

-continued

**566**

-continued

126

5

10

15

20

25

30

35

40

127


45

50

55


60

65




128

129






130



567

-continued

**568**

-continued

131

134

5

10

15

20

132

25

30

35

40

133

45



50

55

60



65

135



569

-continued

**570**

-continued

136

5

10

15

20

25

30

35

40

137

45



50

55

60

65




138



139

571

-continued

**572**

-continued

140

5

10

15

20

141 25

30

35

40

45

142


50

55


60

65


143



144






145



573

-continued

**574**

-continued

146

5

10

15

20

25

147

30

35

40

45

148

50

55




60

65

149




150

151






575

-continued




**576**

-continued



577

-continued

**578**

158

5

10

15

159

20

25

30

35

40

45


160

50


55

60


65



161






162





163

579

-continued




**580**

-continued



581

-continued

**582**

-continued

169

5

10

15

20

170 25

30

35

40

45

171


50

55


60

65


172




173



174



-continued



5

10

15

20

25


30

35

40


45

176



-continued

177



5

10

15

20

25


30

35

40

45

178



50




55

60


65

585

-continued

**586**

-continued



179

182

5

10

15

20

25

180

30

35

40

183

181 45

50




55

60




65

587

-continued




**588**

-continued






589

-continued


**590**

-continued



591

-continued



196


5

10

15

20

197



25


30

35

40

45

198



50


55

60


65

592


-continued



199






200






201

593

-continued

**594**


-continued



595

-continued

208



20

596

-continued


211

5

10

15

20



212

25


209

30

35

40

45





210 50

213

55




60

65






597

-continued




**598**

-continued






599

-continued


**600**

-continued



601

-continued



226

5

10

15

20

25

30

35

40

227


45

50


55

60

65


**602**

-continued





228

229



603

-continued

**604**

-continued

230

5

10

15

20

25

30

35

40

231


45

50

55

60



65



232


233

234



605

-continued

**606**

-continued

235

5

10

15

20

236

25

30

35

40

237

50

55

60

65


238

239




607

-continued




**608**

-continued



609

-continued

**610**

-continued

246

249

5

10

15

247 20

25

30

35

40

250

45


248

50

55


60

65



611

-continued

**612**

-continued

251

253

5

10

15

20

25

30

35

40

252




45

50

55


60

65



613

-continued

**614**

-continued

255

5

10

15

20

256

25

30

35

40

45

257

50

55


60

65

258




259

260



615


-continued

**616**

-continued


261

264



262 25


265



45

263


266



65

617

-continued

**618**

-continued

267

270

5
10
15
20
268

25

30

35

40

269

45

50

55


60

65



619


-continued




272

620


-continued



274




273



275

621

-continued



276

5


10

15

20

622

-continued



279

277

25



30

35

40

45

280



278



50

55

60




65

281






623

-continued

**624**


-continued



625

-continued

288




5

10

15

20



289


25

30

35

40

45



290

50

55


60

65


626

-continued


291



292






293



627

-continued

**628**

-continued

294

5

10

15

20

295

25

30

35

40

45

296

50

55




60

65

297


298

299



629


-continued



300


630

-continued



303

301 20



25


304

30

35

40

302 45



65

50

55


60

305


65

631


-continued




306



307




308




309

632


-continued




310



311







312






313


633

-continued


**634**

-continued




635


321

636


322




323




324




325



326




327



328


637



-continued


329

638




330


331




332




333




334




335



336




639



-continued


337

640




338


339




340




341




342




343



344




641




-continued

345


642




346




347




348




349



350



351



352



643

644

-continued



353

354





355

356




357


358




645

-continued
359


646




360




361



362



363





364

647


-continued
365

648


366



367





368



369

370





649

650

-continued



371

372





373

374



375


376



651


-continued

377





652

378





379

380




381


382



653


-continued
383

654




384


385




386




387



388



655




-continued

389


390

656





391

392




393

394




657



-continued


395

658




396


397




398



399



400





659

660



-continued
401

402





403

404




405

406




661



-continued


407

662




408

409



410




663

664


-continued

411



412




413




415



414




416




665

-continued


417



419




421




666


418



420



422





667

668

-continued



423

424





425

426




427

428




669




-continued
429

670




430


431



432




671



-continued


433

672




434


435




436




437




438



673


-continued
439

674




440


441




442




443



444




675



-continued


445

676




446


447




448




449



450




677



-continued


451

678




452


453




454




455



456




679



-continued


457

680




458


459




460






461



462




681




-continued

463


682



465



467






464

466

468


683




-continued

469

684




471



470


472

473



474


685



-continued


475

686




476


477




478




479



480




687




481


688



482




483



484


689



690


-continued

485




486


487




488




489



490




691



-continued


491

692




492


493



494




693




-continued

495


694



496




497




498

695


-continued
499

696




500


501




502




503



504




697




-continued
505


698



506




507




508

699




-continued
509

700




510


511



512




701




-continued

513


702



514




515



516


703



-continued


517

704




518


519




520




521



522




705




706


-continued
523



524



525




526

707


-continued

527





708

528




529

530




709



-continued


531

710




532

533



534




711

712

-continued


535

536





537

538




539

540




713



-continued


541

714




542


543



544




715




-continued
545

716




546


547




548




717

-continued
549

718



550




551

719

720



-continued

552




553

554




721




-continued
555

722




556


557



558




723




-continued
559


724



560




561



562


725




-continued

563


726



564




565



566


727




-continued

567


728



568




569



570


729




-continued

571


730



572




573




574

731




-continued
575


732



576






577




578

733




-continued

579




581



580

582

583



584




735

736

-continued


585

586





587

588



589

590





737

738

-continued



591

592





593

594




595

596




739




-continued

597


740



598




599



600


741



-continued


601

742




602

603





604




605

606




743



-continued


607

744




608


609



610




745




-continued
611


746



612




613



614


747




-continued

615


748



616




617




618

749




-continued
619

750




620

621



622




751

752


-continued

623


624




625




626




627



628




753



-continued


629

754




630


631




632




633



634




755



-continued


635

756




636


637




638




639



340




757



-continued


641

758




642


643




644




645




646



759


-continued
647

760




648


649




650




651



652




761




-continued

653


762



654




655



656


763



-continued


657

764




658


659



660




765




661

766




662


663



664




767




-continued
665

768




666


667




668




669



670




769




-continued
671


770



672




673



674


771



-continued


675

772




676


677




678




679



680




773



-continued


681

774




682


683



684




775




-continued
685


776



686




687




688

777




-continued
689

778




690


691



692




779




-continued
693


780



694



695



696



781

782

-continued



697

698





699

700



701

702





783

784

-continued



703

704





705

706




707

708




785



-continued


709

786




710


711




712



713



714





787

788

-continued



715

716





717

718



719

720





789

790

-continued



721

722





723

724





725

726




727


728



791


-continued
729

792




730


731




732




733



734




793




-continued
735


794




736




737



738




739



740


795



-continued


741

796




742

743



744





797

798

-continued



745

746





747

748



749

750




799

800

-continued


751

752







753

754



755


756



801


-continued

757




802


758




759




760



761




762



803


-continued

763





804

764





765

766




767

768




805



-continued


769

806




770


771




772




773



774



807




808

-continued



775

776






777

778




809



-continued


779

810




780

781




782

783




784

811


-continued
785

812


786



787



788





813

814

-continued



789

790





791

792



793

794





815

816

-continued



795

796





797

798



799

800





817

818

-continued



801

802





803

804



805


806



819


-continued

807





820

808





809

810



811

812





821

822

-continued



813

814





815

816



817

818




823

824


-continued

819


820




821





822



823




824




825

-continued

825




826




826


827




828







829




830



828





25

8. An organic light emitting device comprising:

a first electrode;

a second electrode; and

an organic material layer provided between the first electrode and the second electrode,

wherein the organic material layer includes the heterocyclic compound of claim 1.

9. The organic light emitting device of claim 8, wherein the organic material layer includes an electron transfer layer, and the electron transfer layer includes the heterocyclic compound.

10. The organic light emitting device of claim 8, wherein the organic material layer includes a charge generation layer, and the charge generation layer includes the heterocyclic compound.

11. The organic light emitting device of claim 8, further comprising one, two or more layers selected from the group consisting of a light emitting layer, a hole injection layer, a

hole transfer layer, an electron injection layer, an electron transfer layer, an electron blocking layer and a hole blocking layer.

12. The organic light emitting device of claim 8 comprising:

the first electrode;

a first stack provided on the first electrode and including a first light emitting layer;

a charge generation layer provided on the first stack;

a second stack provided on the charge generation layer and including a second light emitting layer; and the second electrode provided on the second stack.

13. The organic light emitting device of claim 12, wherein the charge generation layer includes the heterocyclic compound.

14. The organic light emitting device of claim 12, wherein the charge generation layer includes an N-type charge generation layer, and the N-type charge generation layer includes the heterocyclic compound.

* * * * *