

# US Patent & Trademark Office

## Patent Public Search | Text View

---

|                      |                        |
|----------------------|------------------------|
| United States Patent | 12406952               |
| Kind Code            | B2                     |
| Date of Patent       | September 02, 2025     |
| Inventor(s)          | Huang; Chih-Fan et al. |

---

### Chip structure with conductive layer

---

#### Abstract

A chip structure is provided. The chip structure includes a semiconductor substrate. The chip structure includes a first conductive layer over the first dielectric layer. The chip structure includes a conductive via passing through the first conductive layer and electrically connected to the first conductive layer. The chip structure includes a conductive pad over and in direct contact with the conductive via. The chip structure includes a second conductive layer over and spaced apart from the first conductive layer. The chip structure includes a first dielectric layer conformally covering a second lower portion of a sidewall of the second conductive layer. The chip structure includes a third conductive layer over the first dielectric layer.

---

**Inventors:** Huang; Chih-Fan (Kaohsiung, TW), Wang; Mao-Nan (Kaohsiung, TW), Chen; Hui-Chi (Zhudong Township, Hsinchu County, TW), Chen; Dian-Hau (Hsinchu, TW), Chen; Yen-Ming (Chu-Pei, TW)

**Applicant:** TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.  
(Hsinchu, TW)

**Family ID:** 75492180

**Assignee:** TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.  
(Hsinchu, TW)

**Appl. No.:** 18/753052

**Filed:** June 25, 2024

#### Prior Publication Data

|                            |                         |
|----------------------------|-------------------------|
| <b>Document Identifier</b> | <b>Publication Date</b> |
| US 20240347488 A1          | Oct. 17, 2024           |

#### Related U.S. Application Data

## Publication Classification

**Int. Cl.:** H01L23/00 (20060101)

**U.S. Cl.:**

**CPC** H01L24/05 (20130101); H01L24/03 (20130101); H01L24/13 (20130101);  
H01L2224/02311 (20130101); H01L2224/02313 (20130101); H01L2224/02331  
(20130101); H01L2224/03462 (20130101); H01L2224/0401 (20130101);  
H01L2224/05548 (20130101); H01L2224/13016 (20130101)

## Field of Classification Search

**USPC:** None

---

## References Cited

### U.S. PATENT DOCUMENTS

| Patent No.   | Issued Date | Patentee Name    | U.S. Cl. | CPC           |
|--------------|-------------|------------------|----------|---------------|
| 7087977      | 12/2005     | Nakayama et al.  | N/A      | N/A           |
| 7202567      | 12/2006     | Kikuta et al.    | N/A      | N/A           |
| 7280024      | 12/2006     | Braunisch        | N/A      | N/A           |
| 7750434      | 12/2009     | Imaoka et al.    | N/A      | N/A           |
| 8110895      | 12/2011     | Imaoka et al.    | N/A      | N/A           |
| 8222714      | 12/2011     | Shi et al.       | N/A      | N/A           |
| 9368392      | 12/2015     | Tseng            | N/A      | H01L 21/76802 |
| 9391016      | 12/2015     | Shen et al.      | N/A      | N/A           |
| 9502489      | 12/2015     | Funaya et al.    | N/A      | N/A           |
| 9716056      | 12/2016     | Leobandung       | N/A      | N/A           |
| 10290701     | 12/2018     | Chang            | N/A      | H10D 1/696    |
| 10446483     | 12/2018     | Gu et al.        | N/A      | N/A           |
| 10483344     | 12/2018     | Rubin et al.     | N/A      | N/A           |
| 2002/0005565 | 12/2001     | Forbes et al.    | N/A      | N/A           |
| 2007/0114651 | 12/2006     | Marimuthu et al. | N/A      | N/A           |
| 2008/0245880 | 12/2007     | Yamazaki         | N/A      | N/A           |
| 2009/0082691 | 12/2008     | Denison et al.   | N/A      | N/A           |
| 2010/0073122 | 12/2009     | Le Neel et al.   | N/A      | N/A           |
| 2010/0224960 | 12/2009     | Fischer          | 257/532  | H01L 23/5223  |
| 2013/0270675 | 12/2012     | Childs           | 257/532  | H10D 1/692    |
| 2014/0159200 | 12/2013     | Loke et al.      | N/A      | N/A           |
| 2014/0184381 | 12/2013     | Hao et al.       | N/A      | N/A           |
| 2015/0289360 | 12/2014     | Leong et al.     | N/A      | N/A           |
| 2015/0294936 | 12/2014     | Shen et al.      | N/A      | N/A           |
| 2019/0013269 | 12/2018     | Zhang et al.     | N/A      | N/A           |
| 2019/0031269 | 12/2018     | Shang            | N/A      | N/A           |

|              |         |              |           |            |
|--------------|---------|--------------|-----------|------------|
| 2019/0148072 | 12/2018 | Fox, III     | 361/301.4 | H01G 4/005 |
| 2019/0165188 | 12/2018 | Chang et al. | N/A       | N/A        |
| 2019/0221515 | 12/2018 | Gu et al.    | N/A       | N/A        |
| 2019/0305078 | 12/2018 | Wu et al.    | N/A       | N/A        |

---

*Primary Examiner:* Yasmeen; Nishath

*Attorney, Agent or Firm:* Birch, Stewart, Kolasch & Birch, LLP

---

## Background/Summary

CROSS REFERENCE (1) This application is a Continuation of U.S. application Ser. No. 17/874,036, filed on Jul. 26, 2022, which is a Divisional of U.S. application Ser. No. 16/655,998, filed on Oct. 17, 2019, the entirety of which is incorporated by reference herein.

### BACKGROUND

- (1) The semiconductor integrated circuit (IC) industry has experienced rapid growth. Technological advances in IC materials and design have produced generations of ICs. Each generation has smaller and more complex circuits than the previous generation. However, these advances have increased the complexity of processing and manufacturing ICs.
  - (2) In the course of IC evolution, functional density (i.e., the number of interconnected devices per chip area) has generally increased while geometric size (i.e., the smallest component (or line) that can be created using a fabrication process) has decreased. This scaling-down process generally provides benefits by increasing production efficiency and lowering associated costs.
  - (3) However, since feature sizes continue to decrease, fabrication processes continue to become more difficult to perform. Therefore, it is a challenge to form reliable semiconductor devices at smaller and smaller sizes.
- 

## Description

### BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It should be noted that, in accordance with standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.
- (2) FIG. 1A-1 to FIG. 1H-1 are cross-sectional views of various stages of a process for forming a chip structure, in accordance with some embodiments.
- (3) FIG. 1A-2 to FIG. 1C-2 and FIG. 1E-2 to FIG. 1F-2 are top views illustrating the chip structure in FIG. 1A-1 to FIG. 1C-1 and FIG. 1E-1 to FIG. 1F-1, in accordance with some embodiments.
- (4) FIG. 2A is a cross-sectional view of a chip structure, in accordance with some embodiments.
- (5) FIG. 2B is a top view of the chip structure of FIG. 2A, in accordance with some embodiments.
- (6) FIG. 3A-1 to FIG. 3F-1 are cross-sectional views of various stages of a process for forming a chip structure, in accordance with some embodiments.
- (7) FIG. 3A-2 to FIG. 3E-2 are top views illustrating the chip structure in FIG. 3A-1 to FIG. 3E-1, in accordance with some embodiments.
- (8) FIG. 4 is a top view of a conductive layer of FIG. 3A-1, in accordance with some embodiments.
- (9) FIG. 5 is a top view of a conductive layer of FIG. 3A-1, in accordance with some embodiments.
- (10) FIG. 6 is a top view of a conductive layer of FIG. 3A-1, in accordance with some embodiments.

(11) FIG. 7A-1 to FIG. 7F-1 are top views of various stages of a process for forming a chip structure, in accordance with some embodiments.

(12) FIG. 7A-2 to FIG. 7F-2 are cross-sectional views illustrating the chip structure along a sectional line I-I in FIG. 7A-1 to FIG. 7F-1, in accordance with some embodiments.

(13) FIG. 7A-3 to FIG. 7F-3 are cross-sectional views illustrating the chip structure along a sectional line II-II in FIG. 7A-1 to FIG. 7F-1, in accordance with some embodiments.

#### DETAILED DESCRIPTION

(14) The following disclosure provides many different embodiments, or examples, for implementing different features of the subject matter provided. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(15) Furthermore, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. It should be understood that additional operations can be provided before, during, and after the method, and some of the operations described can be replaced or eliminated for other embodiments of the method.

(16) Some embodiments of the disclosure are described. Additional operations can be provided before, during, and/or after the stages described in these embodiments. Some of the stages that are described can be replaced or eliminated for different embodiments. Additional features can be added to the chip structure. Some of the features described below can be replaced or eliminated for different embodiments. Although some embodiments are discussed with operations performed in a particular order, these operations may be performed in another logical order.

(17) FIG. 1A-1 to FIG. 1H-1 are cross-sectional views of various stages of a process for forming a chip structure, in accordance with some embodiments. FIG. 1A-2 to FIG. 1C-2 and FIG. 1E-2 to FIG. 1F-2 are top views illustrating the chip structure in FIG. 1A-1 to FIG. 1C-1 and FIG. 1E-1 to FIG. 1F-1, in accordance with some embodiments.

(18) As shown in FIG. 1A-1, a substrate **110** is provided, in accordance with some embodiments. The substrate **110** includes, for example, a semiconductor substrate. The semiconductor substrate includes, for example, a semiconductor wafer (such as a silicon wafer) or a portion of a semiconductor wafer.

(19) In some embodiments, the substrate **110** is made of an elementary semiconductor material including silicon or germanium in a single crystal, polycrystal, or amorphous structure. In some other embodiments, the substrate **110** is made of a compound semiconductor, such as silicon carbide, gallium arsenide, gallium phosphide, indium phosphide, indium arsenide, an alloy semiconductor, such as SiGe, or GaAsP, or a combination thereof. The substrate **110** may also include multi-layer semiconductors, semiconductor on insulator (SOI) (such as silicon on insulator or germanium on insulator), or a combination thereof.

(20) In some embodiments, the substrate **110** is a device wafer that includes various device elements. In some embodiments, the various device elements are formed in and/or over the

substrate **110**. The device elements are not shown in figures for the purpose of simplicity and clarity. Examples of the various device elements include active devices, passive devices, other suitable elements, or a combination thereof. The active devices may include transistors or diodes (not shown) formed at a surface **112** of the substrate **110**. The passive devices include resistors, capacitors, or other suitable passive devices.

(21) For example, the transistors may be metal oxide semiconductor field effect transistors (MOSFET), complementary metal oxide semiconductor (CMOS) transistors, bipolar junction transistors (BJT), high-voltage transistors, high-frequency transistors, p-channel and/or n-channel field effect transistors (PFETs/NFETs), etc. Various processes, such as front-end-of-line (FEOL) semiconductor fabrication processes, are performed to form the various device elements. The FEOL semiconductor fabrication processes may include deposition, etching, implantation, photolithography, annealing, planarization, one or more other applicable processes, or a combination thereof.

(22) In some embodiments, isolation features (not shown) are formed in the substrate **110**. The isolation features are used to define active regions and electrically isolate various device elements formed in and/or over the substrate **110** in the active regions. In some embodiments, the isolation features include shallow trench isolation (STI) features, local oxidation of silicon (LOCOS) features, other suitable isolation features, or a combination thereof.

(23) As shown in FIG. **1A-1**, an interconnect structure **120** is formed over the substrate **110**, in accordance with some embodiments. The interconnect structure **120** includes a dielectric structure **122**, wiring layers **124**, and conductive vias **126**, in accordance with some embodiments. The dielectric structure **122** may include dielectric layers (not shown) stacked over the substrate **110**, in accordance with some embodiments.

(24) The wiring layers **124** and the conductive vias **126** are in the dielectric structure **122**, in accordance with some embodiments. The wiring layers **124** are spaced apart from each other, in accordance with some embodiments. The wiring layers **124** has a thickness **T1** ranging from about 1000 Å to about 4000 Å, in accordance with some embodiments. The conductive vias **126** are electrically connected between different wiring layers **124** and between the wiring layer **124** and the device elements (not shown) formed at the surface **112** of the substrate **110**, in accordance with some embodiments.

(25) The dielectric structure **122** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), silicon carbide, un-doped silicate glass (USG), or a low-k dielectric material with a k-value lower than that of silicon oxide, in accordance with some embodiments. The wiring layers **124** and the conductive vias **126** are made of metal (e.g., copper, aluminum, gold, silver, or tungsten) or alloy thereof, in accordance with some embodiments.

(26) As shown in FIG. **1A-1**, a dielectric layer **132** and a wiring layer **134** are formed over the interconnect structure **120**, in accordance with some embodiments. The wiring layer **134** is formed in the dielectric layer **132**, in accordance with some embodiments. The wiring layer **134** is also referred to as a top metal layer, in accordance with some embodiments. The wiring layer **134** includes a seed layer **134a** and a conductive layer **134b**, in accordance with some embodiments.

(27) The conductive layer **134b** is formed over the seed layer **134a**, in accordance with some embodiments. The wiring layer **134** includes conductive lines **134c**, **134d**, and **134e**, in accordance with some embodiments. The conductive vias **126** are electrically connected between the wiring layer **124** and the wiring layer **134**, in accordance with some embodiments. The wiring layer **134** is thicker than each wiring layer **124**, in accordance with some embodiments. The wiring layer **134** (or the dielectric layer **132**) has a thickness **T2** ranging from about 5000 Å to about 13000 Å, in accordance with some embodiments.

(28) The dielectric structure **132** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), or un-doped silicate glass (USG), in

accordance with some embodiments. The seed layer **134a** and the conductive layer **134b** are made of metal (e.g., copper, aluminum, gold, silver, or tungsten) or alloy thereof, in accordance with some embodiments.

(29) The seed layer **134a** is formed using a deposition process, such as a physical vapor deposition process or a chemical vapor deposition process, in accordance with some embodiments. The conductive layer **134b** is formed using a plating process, such as an electroplating process, in accordance with some embodiments. In some embodiments (not shown), a barrier layer is formed between the seed layer **134a** and the dielectric layer **132** and between the seed layer **134a** and the dielectric structure **122**. The barrier layer is made of nitrides, such as tantalum nitride, in accordance with some embodiments.

(30) As shown in FIG. **1A-1**, an etch stop layer **140** is formed over the dielectric structure **132** and the wiring layer **134**, in accordance with some embodiments. The etch stop layer **140** is thinner than the wiring layer **134** or the dielectric layer **132**, in accordance with some embodiments. The etch stop layer **140** has a thickness **T3** ranging from about 400 Å to about 1100 Å, in accordance with some embodiments.

(31) The etch stop layer **140** is made of nitrides (e.g., silicon nitride or silicon oxynitride), in accordance with some embodiments. The etch stop layer **140** is formed using a deposition process, such as a chemical vapor deposition process or a physical vapor deposition process, in accordance with some embodiments.

(32) As shown in FIGS. **1A-1** and **1A-2**, a dielectric layer **150** is formed over the etch stop layer **140**, in accordance with some embodiments. The dielectric layer **150** is thinner than the wiring layer **134** or the dielectric layer **132**, in accordance with some embodiments. The dielectric layer **150** has a thickness **T4** ranging from about 3000 Å to about 5000 Å, in accordance with some embodiments.

(33) The dielectric layer **150** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), or un-doped silicate glass (USG), in accordance with some embodiments. The dielectric layer **150** is formed using a deposition process, such as a chemical vapor deposition process (e.g., a plasma enhanced chemical vapor deposition (PECVD) process) or a physical vapor deposition process, in accordance with some embodiments.

(34) As shown in FIGS. **1A-1** and **1A-2**, a conductive layer **160** is formed over the dielectric layer **150**, in accordance with some embodiments. The conductive layer **160** is used as a capacitor electrode, in accordance with some embodiments. The conductive layer **160** has an opening **162**, in accordance with some embodiments. The opening **162** exposes a portion of the dielectric layer **150**, in accordance with some embodiments.

(35) The conductive layer **160** is thinner than the wiring layer **134**, the dielectric layer **132**, or the dielectric layer **150**, in accordance with some embodiments. The conductive layer **160** has a thickness **T5** ranging from about 100 Å to about 800 Å, in accordance with some embodiments. The thickness **T5** ranges from about 200 Å to about 700 Å, in accordance with some embodiments.

(36) The conductive layer **160** is made of a capacitor electrode material, in accordance with some embodiments. The capacitor electrode material includes metal (e.g., copper, aluminum, gold, silver, or tungsten), alloy thereof, nitrides (e.g., titanium nitride), or another suitable capacitor electrode material, in accordance with some embodiments.

(37) The conductive layer **160** is formed using a deposition process (e.g., a physical vapor deposition process or a chemical vapor deposition process), a photolithography process, an etching process, and an optional cleaning and passivation process, in accordance with some embodiments. The cleaning and passivation process is used to clean the residues from the photolithography process and to passivate the surface of the conductive layer **160**, in accordance with some embodiments. The cleaning and passivation process includes a plasma process using N.sub.2O or Ar as a process gas, in accordance with some embodiments.

(38) As shown in FIGS. **1B-1** and **1B-2**, a dielectric layer **170** is formed over the conductive layer

**160** and the dielectric layer **150**, in accordance with some embodiments. The dielectric layer **170** is used as a capacitor dielectric layer, in accordance with some embodiments. The dielectric layer **170** is thinner than the dielectric layer **150** or the conductive layer **160**, in accordance with some embodiments. The dielectric layer **170** has a thickness **T6** ranging from about 10 Å to about 200 Å, in accordance with some embodiments.

(39) In some embodiments, the dielectric layer **170** is a single-layered structure. In some other embodiments, the dielectric layer **170** is a multi-layered structure. The multi-layered structure has layers, and each layer is made of a material different from that of adjacent layer(s), in accordance with some embodiments.

(40) The dielectric layer **170** is made of a capacitor dielectric material, such as a high dielectric constant (high-k) material, in accordance with some embodiments. The high-k material is made of metal oxides, such as zirconium oxide (ZrO<sub>2</sub>), hafnium oxide (HfO<sub>2</sub>), hafnium silicon oxide (HfSiO), hafnium silicon oxynitride (HfSiON), hafnium tantalum oxide (HfTaO), hafnium titanium oxide (HfTiO), hafnium zirconium oxide (HfZrO), aluminum oxide (Al<sub>2</sub>O<sub>3</sub>), hafnium dioxide-alumina (HfO<sub>2</sub>—Al<sub>2</sub>O<sub>3</sub>) alloy, or combinations thereof, in accordance with some embodiments.

(41) In some other embodiments, the high-k material is made of metal nitrides, metal silicates, transition metal-oxides, transition metal-nitrides, transition metal-silicates, oxynitrides of metals, other suitable materials, or combinations thereof. The dielectric layer **170** is formed using a deposition process, such as a chemical vapor deposition (CVD) process, a thermal atomic layer deposition (ALD) process, a plasma enhanced atomic layer deposition (PEALD) process, or another suitable deposition process.

(42) As shown in FIGS. **1B-1** and **1B-2**, a conductive layer **180** is formed over the dielectric layer **170**, in accordance with some embodiments. The conductive layer **180** includes a conductive film **182** and a dummy film **184**, in accordance with some embodiments. The conductive film **182** is used as a capacitor electrode, in accordance with some embodiments.

(43) The conductive film **182** has an opening **182a**, in accordance with some embodiments. The opening **182a** exposes a portion of the dielectric layer **170**, in accordance with some embodiments. The conductive film **182** partially overlaps the conductive layer **160**, in accordance with some embodiments. The conductive film **182** is separated from the conductive layer **160** by the dielectric layer **170**, in accordance with some embodiments.

(44) The dummy film **184** is used as an etch buffer layer in a subsequent through-hole etching process, in accordance with some embodiments. The conductive film **182** and the dummy film **184** are spaced apart from each other, in accordance with some embodiments. The conductive film **182** and the dummy film **184** are electrically insulated from each other, in accordance with some embodiments.

(45) The conductive layer **180** is thinner than the wiring layer **134**, the dielectric layer **132**, or the dielectric layer **150**, in accordance with some embodiments. The conductive layer **180** is thicker than the dielectric layer **170**, in accordance with some embodiments. The conductive layer **180** has a thickness **T7** ranging from about 100 Å to about 800 Å, in accordance with some embodiments. The thickness **T7** ranges from about 200 Å to about 700 Å, in accordance with some embodiments.

(46) The conductive layer **180** is made of a capacitor electrode material, in accordance with some embodiments. The capacitor electrode material includes metal (e.g., copper, aluminum, gold, silver, or tungsten), alloy thereof, nitrides (e.g., titanium nitride), or another suitable capacitor electrode material, in accordance with some embodiments.

(47) The conductive layer **180** is formed using a deposition process (e.g., a physical vapor deposition process or a chemical vapor deposition process), a photolithography process, an etching process, and an optional cleaning and passivation process, in accordance with some embodiments. The cleaning and passivation process is used to clean the residues from the photolithography process and to passivate the surface of the conductive layer **180**, in accordance with some

embodiments. The cleaning and passivation process includes a plasma process using N.sub.2O or Ar as a process gas, in accordance with some embodiments.

(48) As shown in FIGS. 1C-1 and 1C-2, a dielectric layer **190** is formed over the conductive layer **180** and the dielectric layer **170**, in accordance with some embodiments. The dielectric layer **190** is used as a capacitor dielectric layer, in accordance with some embodiments. The dielectric layer **190** is thinner than the dielectric layer **150** or the conductive layer **160** or **180**, in accordance with some embodiments. The dielectric layer **190** has a thickness **T8** ranging from about 10 Å to about 200 Å, in accordance with some embodiments.

(49) In some embodiments, the dielectric layer **190** is a single-layered structure. In some other embodiments, the dielectric layer **190** is a multi-layered structure. The multi-layered structure has layers, and each layer is made of a material different from that of adjacent layer(s), in accordance with some embodiments.

(50) The dielectric layer **190** is made of a capacitor dielectric material, such as a high dielectric constant (high-k) material, in accordance with some embodiments. The high-k material is made of metal oxides, such as zirconium oxide (ZrO.sub.2), hafnium oxide (HfO.sub.2), hafnium silicon oxide (HfSiO), hafnium silicon oxynitride (HfSiON), hafnium tantalum oxide (HfTaO), hafnium titanium oxide (HfTiO), hafnium zirconium oxide (HfZrO), aluminum oxide (Al.sub.2O.sub.3), hafnium dioxide-alumina (HfO.sub.2—Al.sub.2O.sub.3) alloy, or combinations thereof, in accordance with some embodiments.

(51) In some other embodiments, the high-k material is made of metal nitrides, metal silicates, transition metal-oxides, transition metal-nitrides, transition metal-silicates, oxynitrides of metals, other suitable materials, or combinations thereof. The dielectric layer **190** is formed using a deposition process, such as a chemical vapor deposition (CVD) process, a thermal atomic layer deposition (ALD) process, a plasma enhanced atomic layer deposition (PEALD) process, or another suitable deposition process.

(52) As shown in FIGS. 1C-1 and 1C-2, a conductive layer **210** is formed over the dielectric layer **190**, in accordance with some embodiments. The conductive layer **210** includes a conductive film **212** and dummy films **214** and **216**, in accordance with some embodiments. The conductive film **212** is used as a capacitor electrode, in accordance with some embodiments. The conductive film **212** has an opening **212a**, in accordance with some embodiments. The opening **212a** exposes a portion of the dielectric layer **190**, in accordance with some embodiments.

(53) The conductive layer **210** partially overlaps the conductive layer **180**, in accordance with some embodiments. The conductive film **212** overlaps the conductive film **182**, in accordance with some embodiments. The dummy film **214** overlaps the dummy film **184**, in accordance with some embodiments. The conductive layer **210** is separated from the conductive layer **180** by the dielectric layer **190**, in accordance with some embodiments.

(54) The dummy films **214** and **216** are used as an etch buffer layer in a subsequent through-hole etching process, in accordance with some embodiments. The dummy film **216** is in the opening **212a**, in accordance with some embodiments. The conductive film **212** and the dummy films **214** and **216** are spaced apart from each other, in accordance with some embodiments. The conductive film **212** and the dummy films **214** and **216** are electrically insulated from each other, in accordance with some embodiments.

(55) The conductive layer **210** is thinner than the wiring layer **134**, the dielectric layer **132**, or the dielectric layer **150**, in accordance with some embodiments. The conductive layer **210** is thicker than the dielectric layer **190**, in accordance with some embodiments. The conductive layer **210** has a thickness **T9** ranging from about 100 Å to about 800 Å, in accordance with some embodiments. The thickness **T9** ranges from about 200 Å to about 700 Å, in accordance with some embodiments.

(56) The conductive layer **210** is made of a capacitor electrode material, in accordance with some embodiments. The capacitor electrode material includes metal (e.g., copper, aluminum, gold, silver, or tungsten), alloy thereof, nitrides (e.g., titanium nitride), or another suitable capacitor electrode



material, in accordance with some embodiments.

(57) The conductive layer **210** is formed using a deposition process (e.g., a physical vapor deposition process or a chemical vapor deposition process), a photolithography process, an etching process, and an optional cleaning and passivation process, in accordance with some embodiments. The cleaning and passivation process is used to clean the residues from the photolithography process and to passivate the surface of the conductive layer **210**, in accordance with some embodiments. The cleaning and passivation process includes a plasma process using N.sub.2O or Ar as a process gas, in accordance with some embodiments.

(58) As shown in FIG. **1D-1**, a dielectric layer **220** is formed over the conductive layer **210** and the dielectric layer **190**, in accordance with some embodiments. The dielectric layer **220** is thinner than the wiring layer **134** or the dielectric layer **132**, in accordance with some embodiments. The dielectric layer **220** has a thickness **T10** ranging from about 3500 Å to about 5500 Å, in accordance with some embodiments.

(59) The dielectric layer **220** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), or un-doped silicate glass (USG), in accordance with some embodiments. The dielectric layer **220** is formed using a deposition process, such as a chemical vapor deposition process (e.g., a plasma enhanced chemical vapor deposition process) or a physical vapor deposition process, in accordance with some embodiments.

(60) For the sake of clarity, FIG. **1E-2** omits the dielectric layer **220**, in accordance with some embodiments. As shown in FIGS. **1E-1** and **1E-2**, portions of the dielectric layer **220**, the conductive layer **210**, the dielectric layer **190**, the conductive layer **180**, the dielectric layer **170**, the conductive layer **160**, the dielectric layer **150**, and the etch stop layer **140** are removed to form through holes **232**, **234**, and **236**, in accordance with some embodiments. The through holes **232**, **234**, and **236** respectively expose the conductive lines **134c**, **134d**, and **134e**, in accordance with some embodiments.

(61) The through hole **232** passes directly through the dummy films **184** and **214**, in accordance with some embodiments. The through hole **234** passes directly through the dummy film **216** and the conductive film **182**, in accordance with some embodiments. The through hole **236** passes directly through the conductive film **212** and the conductive layer **160**, in accordance with some embodiments.

(62) The formation of the dummy films **184**, **214**, and **216** helps the through holes **232**, **234**, and **236** pass directly through the same number (i.e., **2**) of conductive layers **160**, **180**, and **210**. Therefore, the removal process for forming the through holes **232**, **234**, and **236** may be performed uniformly and over etching of the conductive lines **134c** and **134d** may be prevented.

(63) The through hole **232** directly and passes indirectly through the dielectric layer **220**, the conductive layer **210**, the dielectric layer **190**, the conductive layer **180**, the dielectric layer **170**, the dielectric layer **150**, and the etch stop layer **140**, in accordance with some embodiments.

(64) In some embodiments, the through hole **234** passes indirectly through the conductive layer **160**. The through hole **234** directly and passes indirectly through the dielectric layer **220**, the conductive layer **210**, the dielectric layer **190**, the conductive layer **180**, the dielectric layer **170**, the conductive layer **160**, the dielectric layer **150**, and the etch stop layer **140**, in accordance with some embodiments.

(65) The through hole **236** passes indirectly through the conductive film **182** of the conductive layer **180**, in accordance with some embodiments. The through hole **236** directly and passes indirectly through the dielectric layer **220**, the conductive layer **210**, the dielectric layer **190**, the conductive layer **180**, the dielectric layer **170**, the conductive layer **160**, the dielectric layer **150**, and the etch stop layer **140**, in accordance with some embodiments.

(66) For the sake of clarity, FIG. **1F-2** omits the dielectric layer **220**, in accordance with some embodiments. As shown in FIGS. **1F-1** and **1F-2**, conductive structures **242**, **244** and **246** are respectively formed in and over the through holes **232**, **234**, and **236**, in accordance with some

embodiments. Each of the conductive structure **242**, **244**, or **246** includes a seed layer **241a** and a conductive layer **241b**, in accordance with some embodiments. The conductive layer **241b** is formed over the seed layer **241a**, in accordance with some embodiments.

(67) The conductive structure **242** includes a conductive via **242v** and a conductive pad **242p**, in accordance with some embodiments. The conductive via **242v** is in the through hole **232**, in accordance with some embodiments. The conductive via **242v** is electrically connected to the conductive line **134c**, in accordance with some embodiments. The conductive pad **242p** is over and in direct contact with the conductive via **242v**, in accordance with some embodiments.

(68) The conductive structure **244** includes a conductive via **244v** and a conductive pad **244p**, in accordance with some embodiments. The conductive via **244v** is in the through hole **234**, in accordance with some embodiments. The conductive via **244v** is electrically connected to the conductive film **182** and the conductive line **134d**, in accordance with some embodiments. The conductive pad **244p** is over and in direct contact with the conductive via **244v**, in accordance with some embodiments.

(69) The conductive structure **246** includes a conductive via **246v** and a conductive pad **246p**, in accordance with some embodiments. The conductive via **246v** is in the through hole **236**, in accordance with some embodiments. The conductive via **246v** is electrically connected to the conductive layer **160**, the conductive film **212**, and the conductive line **134e**, in accordance with some embodiments.

(70) The conductive film **212**, the dielectric layer **190**, and the conductive film **182** together form a first capacitor, in accordance with some embodiments. The conductive layer **160**, the dielectric layer **170**, and the conductive film **182** together form a second capacitor, in accordance with some embodiments. The first capacitor is electrically connected in parallel with the second capacitor via the conductive structures **244** and **246**, in accordance with some embodiments.

(71) The conductive pad **246p** is over and in direct contact with the conductive via **246v**, in accordance with some embodiments. The conductive layer **160**, **180** or **210** is thinner than the conductive pad **242p**, **244p** or **246p**, in accordance with some embodiments. The conductive pad **242p**, **244p** or **246p** has a thickness **T11** ranging from about 5000 Å to about 11000 Å, in accordance with some embodiments.

(72) The seed layer **241a** and the conductive layer **241b** are made of metal (e.g., aluminum, copper, gold, silver, or tungsten) or alloy thereof, in accordance with some embodiments. The formation of the seed layer **241a** and the conductive layer **241b** includes performing a deposition process to form a seed material layer (not shown); performing a plating process to form a conductive material layer (not shown); and performing a photolithography process and an etching process, in accordance with some embodiments. The deposition process includes a physical vapor deposition process or a chemical vapor deposition process, in accordance with some embodiments. The plating process includes an electroplating process, in accordance with some embodiments.

(73) As shown in FIG. 1G-1, a dielectric layer **250** is formed over the conductive structures **242**, **244** and **246** and the dielectric layer **220**, in accordance with some embodiments. The dielectric layer **250** has openings **252**, **254**, and **256**, in accordance with some embodiments. The openings **252**, **254**, and **256** respectively expose the conductive structures **242**, **244** and **246**, in accordance with some embodiments. The dielectric layer **250** has a thickness **T12** ranging from about 9000 Å to about 15000 Å, in accordance with some embodiments.

(74) The dielectric layer **250** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), or un-doped silicate glass (USG), in accordance with some embodiments. The dielectric layer **250** is formed using a deposition process, such as a chemical vapor deposition process or a physical vapor deposition process, in accordance with some embodiments.

(75) As shown in FIG. 1G-1, a protective layer **260** is formed over the dielectric layer **250**, in accordance with some embodiments. The protective layer **260** is used to protect the dielectric layer

**250** from damage or being affected by moisture, in accordance with some embodiments. The protective layer **260** has openings **262**, **264**, and **266**, in accordance with some embodiments. The openings **262**, **264**, and **266** respectively expose the conductive structures **242**, **244** and **246**, in accordance with some embodiments. The protective layer **260** has a thickness **T13** ranging from about 3500 Å to about 10000 Å, in accordance with some embodiments.

(76) The protective layer **260** is made of an insulating material, such as nitrides (e.g., silicon nitride or silicon oxynitride), in accordance with some embodiments. The protective layer **260** is formed using a deposition process, such as a chemical vapor deposition process or a physical vapor deposition process, in accordance with some embodiments.

(77) As shown in FIG. **1G-1**, a seed layer **272** is formed over the protective layer **260**, the dielectric layer **250**, and the conductive structures **242**, **244** and **246**, in accordance with some embodiments. The seed layer **272** is made of metal (e.g., copper, aluminum, gold, silver, or tungsten) or alloy thereof, in accordance with some embodiments. The seed layer **272** is formed using a deposition process, such as a physical vapor deposition process or a chemical vapor deposition process, in accordance with some embodiments.

(78) As shown in FIG. **1G-1**, a mask layer **280** is formed over the seed layer **272**, in accordance with some embodiments. The mask layer **280** has openings **282**, **284**, and **286** respectively over the openings **262**, **264**, and **266**, in accordance with some embodiments. The openings **282**, **284**, and **286** expose portions of the seed layer **272**, in accordance with some embodiments. The mask layer **280** is made of a polymer material, such as a photoresist material, in accordance with some embodiments.

(79) As shown in FIG. **1G-1**, conductive layers **274** are formed over the exposed seed layer **272** and in the openings **282**, **284**, and **286**, in accordance with some embodiments. The conductive layers **274** are made of metal (e.g., copper, aluminum, gold, silver, or tungsten) or alloy thereof, in accordance with some embodiments. The conductive layers **274** are formed using a plating process, such as an electroplating process, in accordance with some embodiments.

(80) As shown in FIG. **1G-1**, conductive layers **290a** are formed over the conductive layers **274**, in accordance with some embodiments. The conductive layers **290a** are made of a solder material, such as tin, in accordance with some embodiments. The conductive layers **290a** are formed using a plating process, such as an electroplating process, in accordance with some embodiments.

(81) As shown in FIGS. **1G-1** and **1H-1**, the mask layer **280** and the seed layer **272** under the mask layer **280** are removed, in accordance with some embodiments. After the removal process, each conductive layer **274** and the seed layer **272** thereunder together form a bump structure **270**, in accordance with some embodiments. The bump structure **270** is over and in direct contact with the conductive structure **242**, **244** or **246**, in accordance with some embodiments. As shown in FIG. **1H-1**, a reflow process is performed over the conductive layer **290a** to form solder balls **290**, in accordance with some embodiments. In this step, a chip structure **100** is substantially formed, in accordance with some embodiments.

(82) The width **W1** of the conductive via **242v**, **244v** or **246v** is greater than the width **W2** of the conductive via **126** of the interconnect structure **120**, in accordance with some embodiments. The width **W1** ranges from about ?? Å to about ?? Å, in accordance with some embodiments. The width **W2** ranges from about ?? Å to about ?? Å, in accordance with some embodiments. (Note to TSMC inventor: Please provide possible range of the widths **W1** and **W2**, thank you!)

(83) Since the first capacitor and the second capacitor are integrated into the chip structure **100**, the conductive path between the device elements, which are formed at the surface **112** of the substrate **110**, and the first and second capacitors is greatly reduced, in accordance with some embodiments. Therefore, the resistance of aforementioned conductive path is greatly reduced, in accordance with some embodiments.

(84) Furthermore, since the conductive via **242v**, **244v** or **246v** is wider than the conductive via **126** of the interconnect structure **120**, the contact area between the conductive via **242v**, **244v** or **246v**

and the first and second capacitors is larger than the contact area between the conductive via **126** and a capacitor (not shown) formed in the interconnect structure **120**. Therefore, the charging speed of the first and second capacitors is improved, and the operation frequency of the first and second capacitors is improved as well, in accordance with some embodiments.

(85) FIG. 2A is a cross-sectional view of a chip structure **200**, in accordance with some embodiments. FIG. 2B is a top view of the chip structure **200** of FIG. 2A, in accordance with some embodiments. As shown in FIGS. 2A and 2B, the chip structure **200** is similar to the chip structure **100** of FIG. 1H-1, except that the conductive layer **160** of the chip structure **200** further has a dummy film **164**, and the conductive layer **210** of the chip structure **200** does not have the dummy film **216**, in accordance with some embodiments.

(86) The dummy film **164** is in the opening **162** of the conductive layer **160**, in accordance with some embodiments. The conductive structure **244** passes directly through the dummy film **164** of the conductive layer **160** and the conductive film **182** of the conductive layer **180**, in accordance with some embodiments.

(87) FIG. 3A-1 to FIG. 3F-1 are cross-sectional views of various stages of a process for forming a chip structure, in accordance with some embodiments. FIG. 3A-2 to FIG. 3E-2 are top views illustrating the chip structure in FIG. 3A-1 to FIG. 3E-1, in accordance with some embodiments.

(88) As shown in FIGS. 3A-1 and 3A-2, a step similar to the step of FIG. 1A-1 is performed to form a substrate **110**, an interconnect structure **120**, a dielectric layer **132**, a wiring layer **134**, an etch stop layer **140**, a dielectric layer **150**, and a conductive layer **310**, in accordance with some embodiments.

(89) The step of FIGS. 3A-1 and 3A-2 is similar to that of the FIGS. 1A-1 and 1A-2, except that in comparison with the conductive layer **160** formed in the step of FIGS. 1A-1 and 1A-2, the conductive layer **310** formed in the step of FIGS. 3A-1 and 3A-2 includes a conductive line **312**, and the conductive line **312** has a spiral shape, in accordance with some embodiments. The conductive layer **310** is used as an inductor, in accordance with some embodiments.

(90) The conductive line **312** has end portions **312a** and **312b** and a main portion **312c**, in accordance with some embodiments. The end portions **312a** and **312b** are connected to the main portion **312c**, in accordance with some embodiments. The end portion **312a** or **312b** is wider than the main portion **312c**, in accordance with some embodiments. That is, a line width **W3** of the end portion **312a** or **312b** is greater than a line width **W4** of the main portion **312c**, in accordance with some embodiments.

(91) The conductive line **312** may have a round spiral shape (as shown in FIG. 3A-2), a square spiral shape (as shown in FIG. 4), a hexagonal spiral shape (as shown in FIG. 5), or an octagonal spiral shape (as shown in FIG. 6), in accordance with some embodiments.

(92) The conductive layer **310** is made of an inductor material, in accordance with some embodiments. The inductor material includes metal (e.g., copper, aluminum, gold, silver, or tungsten), alloy thereof, nitrides (e.g., titanium nitride), or another suitable inductor material, in accordance with some embodiments.

(93) As shown in FIGS. 3B-1 and 3B-2, a dielectric layer **320** is formed over the conductive layer **310** and the dielectric layer **150**, in accordance with some embodiments. The dielectric layer **320** conformally covers the conductive layer **310**, in accordance with some embodiments. In some embodiments, the dielectric layer **320** is a single-layered structure. In some other embodiments, the dielectric layer **320** is a multi-layered structure. The multi-layered structure has layers, and each layer is made of a material different from that of adjacent layer(s), in accordance with some embodiments.

(94) The dielectric layer **320** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), silicon carbide, un-doped silicate glass (USG), or a low-k dielectric material with a k-value lower than that of silicon oxide, in accordance with some embodiments. The dielectric layer **320** is formed using a deposition process, such as a

chemical vapor deposition (CVD) process, a thermal atomic layer deposition (ALD) process, a plasma enhanced atomic layer deposition (PEALD) process, or another suitable deposition process. (95) As shown in FIGS. 3B-1 and 3B-2, a conductive layer **330** is formed over the dielectric layer **320**, in accordance with some embodiments. The conductive layer **330** includes a conductive line **332**, and the conductive line **332** has a spiral shape, in accordance with some embodiments. The conductive layer **330** is used as an inductor, in accordance with some embodiments.

(96) The conductive line **332** has end portions **332a** and **332b** and a main portion **332c**, in accordance with some embodiments. The end portions **332a** and **332b** are connected to the main portion **332c**, in accordance with some embodiments. The end portion **332a** or **332b** is wider than the main portion **332c**, in accordance with some embodiments. That is, a line width **W5** of the end portion **332a** or **332b** is greater than a line width **W6** of the main portion **332c**, in accordance with some embodiments.

(97) The conductive line **332** may have a round spiral shape (as shown in FIG. 3B-2), a square spiral shape (which is similar to that of the conductive line **312** of FIG. 4), a hexagonal spiral shape (which is similar to that of the conductive line **312** of FIG. 5), or an octagonal spiral shape (which is similar to that of the conductive line **312** of FIG. 6), in accordance with some embodiments.

(98) The conductive layer **330** is made of an inductor material, in accordance with some embodiments. The inductor material includes metal (e.g., copper, aluminum, gold, silver, or tungsten), alloy thereof, nitrides (e.g., titanium nitride), or another suitable inductor material, in accordance with some embodiments.

(99) As shown in FIGS. 3C-1 and 3C-2, a dielectric layer **340** is formed over the conductive layer **330** and the dielectric layer **320**, in accordance with some embodiments. The dielectric layer **340** conformally covers the conductive layer **330** and the dielectric layer **320**, in accordance with some embodiments.

(100) In some embodiments, the dielectric layer **340** is a single-layered structure. In some other embodiments, the dielectric layer **340** is a multi-layered structure. The multi-layered structure has layers, and each layer is made of a material different from that of adjacent layer(s), in accordance with some embodiments.

(101) The dielectric layer **340** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), silicon carbide, un-doped silicate glass (USG), or a low-k dielectric material with a k-value lower than that of silicon oxide, in accordance with some embodiments.

(102) The dielectric layer **340** is formed using a deposition process, such as a chemical vapor deposition (CVD) process, a thermal atomic layer deposition (ALD) process, a plasma enhanced atomic layer deposition (PEALD) process, or another suitable deposition process.

(103) As shown in FIGS. 3C-1 and 3C-2, a conductive layer **350** is formed over the dielectric layer **340**, in accordance with some embodiments. The conductive layer **350** includes a conductive line **352**, and the conductive line **352** has a spiral shape, in accordance with some embodiments. The conductive layer **350** is used as an inductor, in accordance with some embodiments.

(104) The conductive line **352** has end portions **352a** and **352b** and a main portion **352c**, in accordance with some embodiments. The end portions **352a** and **352b** are connected to the main portion **352c**, in accordance with some embodiments. The end portion **352a** or **352b** is wider than the main portion **352c**, in accordance with some embodiments. That is, a line width **W7** of the end portion **352a** or **352b** is greater than a line width **W8** of the main portion **352c**, in accordance with some embodiments.

(105) The conductive line **352** may have a round spiral shape (as shown in FIG. 3C-2), a square spiral shape (which is similar to that of the conductive line **312** of FIG. 4), a hexagonal spiral shape (which is similar to that of the conductive line **312** of FIG. 5), or an octagonal spiral shape (which is similar to that of the conductive line **312** of FIG. 6), in accordance with some embodiments.

(106) The conductive layer **350** is made of an inductor material, in accordance with some

embodiments. The inductor material includes metal (e.g., copper, aluminum, gold, silver, or tungsten), alloy thereof, nitrides (e.g., titanium nitride), or another suitable inductor material, in accordance with some embodiments.

(107) As shown in FIG. 3D-1, the step of FIG. 1D-1 is performed to form a dielectric layer 220 over the conductive layer 350 and the dielectric layer 340, in accordance with some embodiments. The dielectric layer 220 covers the entire conductive layer 350 and the entire dielectric layer 340, in accordance with some embodiments. For the sake of clarity, FIG. 3D-2 omits the dielectric layer 220, in accordance with some embodiments.

(108) As shown in FIGS. 3D-1 and 3D-2, portions of the dielectric layer 220, the conductive layer 350, the dielectric layer 340, the conductive layer 330, the dielectric layer 320, the conductive layer 310, the dielectric layer 150, and the etch stop layer 140 are removed to form through holes 362 and 364, in accordance with some embodiments. The through holes 362 and 364 respectively expose the conductive lines 134c and 134d, in accordance with some embodiments.

(109) The through hole 362 passes through the end portions 312a, 332a, and 352a, in accordance with some embodiments. The through hole 364 passes through the end portions 312b, 332b, and 352b, in accordance with some embodiments. The through holes 362 and 364 are formed using a photolithography process and an etching process, in accordance with some embodiments.

(110) For the sake of clarity, FIG. 3E-2 omits the dielectric layer 220, in accordance with some embodiments. As shown in FIGS. 3E-1 and 3E-2, the step of FIG. 1F-1 is performed to form conductive structures 242 and 244, in accordance with some embodiments.

(111) The conductive structures 242 and 244 are respectively formed in and over the through holes 362 and 364, in accordance with some embodiments. Each of the conductive structure 242 or 244 includes a seed layer 241a and a conductive layer 241b, in accordance with some embodiments. The conductive layer 241b is formed over the seed layer 241a, in accordance with some embodiments.

(112) The conductive structure 242 includes a conductive via 242v and a conductive pad 242p, in accordance with some embodiments. The conductive via 242v is in the through hole 362, in accordance with some embodiments. The conductive via 242v passes through the end portions 312a, 332a, and 352a, in accordance with some embodiments. The conductive via 242v is electrically connected to the conductive layers 310, 330, and 350, in accordance with some embodiments. The conductive pad 242p is over and in direct contact with the conductive via 242v, in accordance with some embodiments.

(113) The conductive structure 244 includes a conductive via 244v and a conductive pad 244p, in accordance with some embodiments. The conductive via 244v is in the through hole 364, in accordance with some embodiments. The conductive via 244v passes through the end portions 312b, 332b, and 352b, in accordance with some embodiments.

(114) The conductive via 244v is electrically connected to the conductive layers 310, 330, and 350, in accordance with some embodiments. The conductive pad 244p is over and in direct contact with the conductive via 244v, in accordance with some embodiments.

(115) In some embodiments, the conductive layer 310 is a first inductor, the conductive layer 330 is a second inductor, and the conductive layer 350 is a third inductor. The first inductor, the second inductor and the third inductor are electrically connected in parallel with each other via the conductive structures 242 and 244, in accordance with some embodiments.

(116) As shown in FIG. 3F-1, the steps of FIGS. 1G-1 and 1H-1 are performed to form a dielectric layer 250, a protective layer 260, bump structures 270, and solder balls 290, in accordance with some embodiments. The dielectric layer 250 is formed over the conductive structures 242 and 244 and the dielectric layer 220, in accordance with some embodiments. The dielectric layer 250 has openings 252 and 254, in accordance with some embodiments. The openings 252 and 254 respectively expose the conductive structures 242 and 244, in accordance with some embodiments.

(117) The protective layer 260 is formed over the dielectric layer 250, in accordance with some

embodiments. The protective layer **260** is used to protect the dielectric layer **250** from damage or being affected by moisture, in accordance with some embodiments. The protective layer **260** has openings **262** and **264**, in accordance with some embodiments. The openings **262** and **264** respectively expose the conductive structures **242** and **244**, in accordance with some embodiments. (118) The bump structures **270** are respectively in the openings **262** and **264**, in accordance with some embodiments. Each bump structure **270** includes a seed layer **272** and a conductive layer **274**, in accordance with some embodiments. The conductive layer **274** is over the seed layer **272**, in accordance with some embodiments. The solder balls **290** are respectively over the bump structures **270**, in accordance with some embodiments. In this step, a chip structure **300** is substantially formed, in accordance with some embodiments. The width **W1** of the conductive via **242v** or **244v** is greater than the width **W2** of the conductive via **126** of the interconnect structure **120**, in accordance with some embodiments.

(119) Since the first inductor, the second inductor, and the third inductor are integrated into the chip structure **300**, the conductive path between the device elements, which are formed at the surface **112** of the substrate **110**, and the first, second and third inductors is greatly reduced, in accordance with some embodiments. Therefore, the resistance of aforementioned conductive path is greatly reduced, in accordance with some embodiments.

(120) Furthermore, since the conductive via **242v** or **244v** is wider than the conductive via **126** of the interconnect structure **120**, the contact area between the conductive via **242v** or **244v** and the first, second and third inductors is larger than the contact area between the conductive via **126** and an inductor (not shown) formed in the interconnect structure **120**. Therefore, the resistance between the conductive via **242v** or **244v** and the first, second and third inductors is reduced, in accordance with some embodiments.

(121) FIG. 7A-1 to FIG. 7F-1 are top views of various stages of a process for forming a chip structure, in accordance with some embodiments. FIG. 7A-2 to FIG. 7F-2 are cross-sectional views illustrating the chip structure along a sectional line I-I in FIG. 7A-1 to FIG. 7F-1, in accordance with some embodiments. FIG. 7A-3 to FIG. 7F-3 are cross-sectional views illustrating the chip structure along a sectional line II-II in FIG. 7A-1 to FIG. 7F-1, in accordance with some embodiments.

(122) As shown in FIGS. 7A-1, 7A-2, and 7A-3, a step similar to the step of FIG. 1A-1 is performed to form a substrate **110**, an interconnect structure **120**, a dielectric layer **132**, a wiring layer **134**, an etch stop layer **140**, a dielectric layer **150**, and a conductive layer **710**, in accordance with some embodiments. The wiring layer **134** includes conductive lines **134c**, **134d**, **134e**, and **134f**, in accordance with some embodiments.

(123) The step of FIGS. 7A-1, 7A-2, and 7A-3 is similar to the FIGS. 1A-1 and 1A-2, except that in comparison with the conductive layer **160** formed in the step of FIGS. 1A-1 and 1A-2, the conductive layer **710** formed in the step of FIGS. 7A-1, 7A-2, and 7A-3 includes a conductive line **712**, in accordance with some embodiments. The conductive line **712** has a wavy shape (or a meander shape), in accordance with some embodiments. The conductive line **712** is used as a resistor, in accordance with some embodiments.

(124) The conductive line **712** has end portions **712a** and **712b** and a main portion **712c**, in accordance with some embodiments. The end portions **712a** and **712b** are connected to the main portion **712c**, in accordance with some embodiments. The end portion **712a** or **712b** is wider than the main portion **712c**, in accordance with some embodiments. That is, a line width **W9** of the end portion **712a** or **712b** is greater than a line width **W10** of the main portion **712c**, in accordance with some embodiments.

(125) The conductive layer **710** is made of a resistor material, in accordance with some embodiments. The resistor material includes semiconductor (e.g., polysilicon), nitrides (e.g., titanium nitride), metal (e.g., tantalum), alloy (e.g., nichrome) or another suitable resistor material, in accordance with some embodiments. In some embodiments, the resistance of the resistor

material is higher than that of the materials of the wiring layers **124** and **134** or the conductive vias **126**.

(126) In some other embodiments, the conductive layer **710** and the wiring layers **124** and **134** (or the conductive vias **126**) are made of the same material (e.g., copper, aluminum, gold, silver, tungsten, alloys thereof), and the resistance of the conductive layer **710** may be adjusted by adjusting the shape or the size (e.g., the length) of the conductive line **712**, in accordance with some embodiments.

(127) As shown in FIGS. **7B-1**, **7B-2**, and **7B-3**, a dielectric layer **720** is formed over the conductive layer **710** and the dielectric layer **150**, in accordance with some embodiments. The dielectric layer **720** covers the entire conductive layer **710** and the entire dielectric layer **150**, in accordance with some embodiments.

(128) The dielectric layer **720** conformally covers the conductive layer **710** and the dielectric layer **150**, in accordance with some embodiments. In some embodiments, the dielectric layer **720** is a single-layered structure. In some other embodiments, the dielectric layer **720** is a multi-layered structure. The multi-layered structure has layers, and each layer is made of a material different from that of adjacent layer(s), in accordance with some embodiments.

(129) The dielectric layer **720** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), silicon carbide, un-doped silicate glass (USG), or a low-k dielectric material with a k-value lower than that of silicon oxide, in accordance with some embodiments.

(130) The dielectric layer **720** is formed using a deposition process, such as a chemical vapor deposition (CVD) process, a thermal atomic layer deposition (ALD) process, a plasma enhanced atomic layer deposition (PEALD) process, or another suitable deposition process.

(131) As shown in FIGS. **7B-1**, **7B-2**, and **7B-3**, a conductive layer **730** is formed over the dielectric layer **720**, in accordance with some embodiments. The conductive layer **730** includes a conductive line **732** and dummy films **734** and **736**, in accordance with some embodiments. The conductive line **732** has a wavy shape (or a meander shape), in accordance with some embodiments. The conductive line **732** is used as a resistor, in accordance with some embodiments.

(132) The conductive line **732** has end portions **732a** and **732b** and a main portion **732c**, in accordance with some embodiments. The end portions **732a** and **732b** are connected to the main portion **732c**, in accordance with some embodiments. The end portion **732a** or **732b** is wider than the main portion **732c**, in accordance with some embodiments. That is, a line width **W11** of the end portion **732a** or **732b** is greater than a line width **W12** of the main portion **732c**, in accordance with some embodiments. The dummy film **734** overlaps the end portion **712a**, in accordance with some embodiments. The end portion **732b** overlaps the end portion **712b**, in accordance with some embodiments.

(133) The conductive layer **730** is made of a resistor material, in accordance with some embodiments. The resistor material includes semiconductor (e.g., polysilicon), nitrides (e.g., titanium nitride), metal (e.g., tantalum), alloy (e.g., nichrome), or another suitable resistor material, in accordance with some embodiments. In some embodiments, the resistance of the resistor material is higher than that of the materials of the wiring layers **124** and **134** or the conductive vias **126**.

(134) In some other embodiments, the conductive layer **730** and the wiring layers **124** and **134** (or the conductive vias **126**) are made of the same material (e.g., copper, aluminum, gold, silver, tungsten, alloys thereof), and the resistance of the conductive layer **730** may be adjusted by adjusting the shape or the size (e.g., the length) of the conductive line **732**, in accordance with some embodiments.

(135) As shown in FIGS. **7C-1**, **7C-2**, and **7C-3**, a dielectric layer **740** is formed over the conductive layer **730** and the dielectric layer **720**, in accordance with some embodiments. The dielectric layer **740** covers the entire conductive layer **730** and the entire dielectric layer **720**, in



accordance with some embodiments.

(136) The dielectric layer **740** conformally covers the conductive layer **730** and the dielectric layer **720**, in accordance with some embodiments. In some embodiments, the dielectric layer **740** is a single-layered structure. In some other embodiments, the dielectric layer **740** is a multi-layered structure. The multi-layered structure has layers, and each layer is made of a material different from that of adjacent layer(s), in accordance with some embodiments.

(137) The dielectric layer **740** is made of an insulating material, such as oxides (e.g., silicon oxide), nitrides (e.g., silicon nitride or silicon oxynitride), silicon carbide, un-doped silicate glass (USG), or a low-k dielectric material with a k-value lower than that of silicon oxide, in accordance with some embodiments. The dielectric layer **740** is formed using a deposition process, such as a chemical vapor deposition (CVD) process, a thermal atomic layer deposition (ALD) process, a plasma enhanced atomic layer deposition (PEALD) process, or another suitable deposition process.

(138) As shown in FIGS. **7C-1**, **7C-2**, and **7C-3**, a conductive layer **750** is formed over the dielectric layer **740**, in accordance with some embodiments. The conductive layer **750** includes a conductive line **752**, in accordance with some embodiments. The conductive line **752** has a wavy shape (or a meander shape), in accordance with some embodiments. The conductive line **752** is used as a resistor, in accordance with some embodiments.

(139) The conductive line **752** has end portions **752a** and **752b** and a main portion **752c**, in accordance with some embodiments. The end portions **752a** and **752b** are connected to the main portion **752c**, in accordance with some embodiments. The end portion **752a** or **752b** is wider than the main portion **752c**, in accordance with some embodiments. That is, a line width **W13** of the end portion **752a** or **752b** is greater than a line width **W14** of the main portion **752c**, in accordance with some embodiments.

(140) The conductive layer **750** is made of a resistor material, in accordance with some embodiments. The resistor material includes semiconductor (e.g., polysilicon), nitrides (e.g., titanium nitride), metal (e.g., tantalum), alloy (e.g., nichrome), or another suitable resistor material, in accordance with some embodiments. In some embodiments, the resistance of the resistor material is higher than that of the materials of the wiring layers **124** and **134** or the conductive vias **126**.

(141) In some other embodiments, the conductive layer **750** and the wiring layers **124** and **134** (or the conductive vias **126**) are made of the same material (e.g., copper, aluminum, gold, silver, tungsten, alloys thereof), and the resistance of the conductive layer **750** may be adjusted by adjusting the shape or the size (e.g., the length) of the conductive line **752**, in accordance with some embodiments.

(142) As shown in FIGS. **7D-1**, **7D-2**, and **7D-3**, the step of FIG. **1D-1** is performed to form a dielectric layer **220** over the conductive layer **750** and the dielectric layer **740**, in accordance with some embodiments. For the sake of clarity, FIG. **7D-1** omits the dielectric layer **220**, in accordance with some embodiments.

(143) As shown in FIGS. **7D-1**, **7D-2** and **7D-3**, portions of the dielectric layer **220**, the conductive layer **750**, the dielectric layer **740**, the conductive layer **730**, the dielectric layer **720**, the conductive layer **710**, the dielectric layer **150**, and the etch stop layer **140** are removed to form through holes **762**, **764**, **766** and **768**, in accordance with some embodiments. The through holes **762**, **764**, **766** and **768** respectively expose the conductive lines **134c**, **134d**, **134e** and **134f**, in accordance with some embodiments.

(144) The through hole **762** passes through the end portion **712a** and the dummy film **734**, in accordance with some embodiments. The through hole **764** passes through the end portions **732a** and **752a**, in accordance with some embodiments. The through hole **766** passes through the end portions **712b** and **732b**, in accordance with some embodiments.

(145) The through hole **768** passes through the end portion **752b** and the dummy film **736**, in accordance with some embodiments. The through holes **762**, **764**, **766** and **768** are formed using a

photolithography process and an etching process, in accordance with some embodiments.

(146) For the sake of clarity, FIG. 7E-1 omits the dielectric layer 220, in accordance with some embodiments. As shown in FIGS. 7E-1, 7E-2, and 7E-3, the step of FIG. 1F-1 is performed to form conductive structures 242, 244, 246 and 248, in accordance with some embodiments.

(147) The conductive structures 242, 244, 246 and 248 are respectively formed in and over the through holes 762, 764, 766 and 768, in accordance with some embodiments. Each of the conductive structure 242, 244, 246 or 248 includes a seed layer 241a and a conductive layer 241b, in accordance with some embodiments. The conductive layer 241b is formed over the seed layer 241a, in accordance with some embodiments.

(148) The conductive structure 242 includes a conductive via 242v and a conductive pad 242p, in accordance with some embodiments. The conductive via 242v is in the through hole 762, in accordance with some embodiments. The conductive via 242v passes through the end portion 712a and the dummy film 734, in accordance with some embodiments. The conductive via 242v is electrically connected to the conductive line 712, in accordance with some embodiments. The conductive pad 242p is over and in direct contact with the conductive via 242v, in accordance with some embodiments.

(149) The conductive structure 244 includes a conductive via 244v and a conductive pad 244p, in accordance with some embodiments. The conductive via 244v is in the through hole 764, in accordance with some embodiments. The conductive via 244v passes through the end portions 732a and 752a, in accordance with some embodiments. The conductive via 244v is electrically connected to the conductive lines 732 and 752, in accordance with some embodiments. The conductive pad 244p is over and in direct contact with the conductive via 244v, in accordance with some embodiments.

(150) The conductive structure 246 includes a conductive via 246v and a conductive pad 246p, in accordance with some embodiments. The conductive via 246v is in the through hole 766, in accordance with some embodiments. The conductive via 246v passes through the end portions 712b and 732b, in accordance with some embodiments. The conductive via 246v is electrically connected to the conductive lines 712 and 732, in accordance with some embodiments. The conductive pad 246p is over and in direct contact with the conductive via 246v, in accordance with some embodiments.

(151) The conductive structure 248 includes a conductive via 248v and a conductive pad 248p, in accordance with some embodiments. The conductive via 248v is in the through hole 768, in accordance with some embodiments. The conductive via 248v passes through the end portion 752b and the dummy film 736, in accordance with some embodiments. The conductive via 248v is electrically connected to the conductive line 752, in accordance with some embodiments. The conductive pad 248p is over and in direct contact with the conductive via 248v, in accordance with some embodiments.

(152) In some embodiments, the conductive line 712 is a first resistor, the conductive line 732 is a second resistor, and the conductive line 752 is a third resistor. The first resistor, the second resistor and the third resistor are electrically connected in series with each other via the conductive structures 242, 244, 246 and 248, in accordance with some embodiments.

(153) In some embodiments, a current flows from the conductive structure 242 to the conductive structure 248 sequentially through the conductive line 712 (including the end portion 712a, the main portion 712c, and the end portion 712b), the conductive structure 246, the conductive line 732 (including the end portion 732b, the main portion 732c, and the end portion 732a), the conductive structure 244, and the conductive line 752 (including the end portion 752a, the main portion 752c, and the end portion 752b), in accordance with some embodiments.

(154) As shown in FIGS. 7F-1, 7F-2, and 7F-3, the steps of FIGS. 1G-1 and 1H-1 are performed to form a dielectric layer 250, a protective layer 260, bump structures 270, and solder balls 290, in accordance with some embodiments. The dielectric layer 250 is formed over the conductive

structures **242**, **244**, **246** and **248** and the dielectric layer **220**, in accordance with some embodiments. The dielectric layer **250** has openings **252**, **254**, **256** and **258**, in accordance with some embodiments. The openings **252**, **254**, **256** and **258** respectively expose the conductive structures **242**, **244**, **246** and **248**, in accordance with some embodiments.

(155) The protective layer **260** is formed over the dielectric layer **250**, in accordance with some embodiments. The protective layer **260** is used to protect the dielectric layer **250** from damage or being affected by moisture, in accordance with some embodiments. The protective layer **260** has openings **262**, **264**, **266** and **268**, in accordance with some embodiments. The openings **262**, **264**, **266** and **268** respectively expose the conductive structures **242**, **244**, **246** and **248**, in accordance with some embodiments.

(156) The bump structures **270** are respectively formed in the openings **262**, **264**, **266** and **268**, in accordance with some embodiments. Each bump structure **270** includes a seed layer **272** and a conductive layer **274**, in accordance with some embodiments. The conductive layer **274** is over the seed layer **272**, in accordance with some embodiments. The solder balls **290** are respectively over the bump structures **270**, in accordance with some embodiments. In this step, a chip structure **700** is substantially formed, in accordance with some embodiments.

(157) Since the first resistor, the second resistor, and the third resistor are integrated into the chip structure **700**, the conductive path between the device elements, which are formed at the surface **112** of the substrate **110**, and the first, second and third resistors may be precisely controlled which may prevent undesired resistance, in accordance with some embodiments. Therefore, the performance of the chip structure **700** is improved, in accordance with some embodiments.

(158) The thickness of the conductive layer **310**, **330**, **350**, **710**, **730** or **750** (as shown in FIGS. 3F-1 and 7F-2) is substantially similar to or the same as that of the conductive layer **160** (as shown in FIG. 1H-1), in accordance with some embodiments. The thickness of the dielectric layer **320**, **340**, **720** or **740** (as shown in FIGS. 3F-1 and 7F-2) is substantially similar to or the same as that of the dielectric layer **170** or **190** (as shown in FIG. 1H-1), in accordance with some embodiments.

(159) Processes and materials for forming the chip structures **200**, **300** and **700** may be similar to, or the same as, those for forming the chip structure **100** described above.

(160) In accordance with some embodiments, chip structures and methods for forming the same are provided. The methods (for forming the chip structure) form a passive device between a conductive pad and a top metal layer of a chip structure, in accordance with some embodiments. The passive device is electrically connected to a conductive via between the conductive pad and the top metal layer, in accordance with some embodiments. Since the passive device is integrated into the chip structure, the conductive path between the passive device and device elements formed in the chip structure is reduced, which reduces the resistance of the conductive path. Therefore, the performance of the chip structure is improved.

(161) In accordance with some embodiments, a method for forming a chip structure is provided. The method includes providing a semiconductor substrate, a first conductive line, and a first dielectric layer. The first conductive line is over the semiconductor substrate, and the first dielectric layer is over the first conductive line and the semiconductor substrate. The method includes forming a first conductive layer over the first dielectric layer. The first conductive layer is thinner than the first conductive line. The method includes forming a second conductive layer over the first conductive layer. The first conductive layer and the second conductive layer are electrically insulated from each other. The method includes forming a second dielectric layer over the second conductive layer and the first conductive layer. The method includes forming a first through hole passing through the second dielectric layer, the first conductive layer, and the first dielectric layer. The method includes forming a first conductive structure in and over the first through hole. The first conductive structure includes a first conductive via and a first conductive pad, the first conductive via is in the first through hole and electrically connected to the first conductive layer and the first conductive line, and the first conductive pad is over and in direct contact with the first

conductive via.

(162) In accordance with some embodiments, a method for forming a chip structure is provided. The method includes providing a semiconductor substrate, a first conductive line, and a first dielectric layer. The first conductive line is over the semiconductor substrate, and the first dielectric layer is over the first conductive line and the semiconductor substrate. The method includes forming a second conductive line over the first dielectric layer. The second conductive line is thinner than the first conductive line, and the second conductive line has a spiral shape. The method includes forming a second dielectric layer over the second conductive line and the first dielectric layer. The method includes forming a first through hole passing through the second dielectric layer, the second conductive line, and the first dielectric layer. The method includes forming a first conductive structure in and over the first through hole. The first conductive structure includes a first conductive via and a first conductive pad, the first conductive via is in the first through hole and electrically connected to the second conductive line and the first conductive line, and the first conductive pad is over and connected to the first conductive via.

(163) In accordance with some embodiments, a method for forming a chip structure is provided. The method includes providing a semiconductor substrate, a first conductive line, and a first dielectric layer. The first conductive line is over the semiconductor substrate, and the first dielectric layer is over the first conductive line and the semiconductor substrate. The method includes forming a conductive layer over the first dielectric layer. The method includes forming a second dielectric layer over the conductive layer and the first dielectric layer. The method includes forming a first through hole passing through the second dielectric layer, the conductive layer, and the first dielectric layer. The method includes forming a first conductive structure in and over the first through hole. The first conductive structure includes a first conductive via and a first conductive pad, the first conductive via is in the first through hole and electrically connected to the conductive layer and the first conductive line, the first conductive pad is over the first conductive via, the conductive layer is made of a first material having a first resistance, and the first resistance is higher than a second resistance of a second material of the first conductive structure.

(164) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

## Claims

1. A chip structure, comprising: a semiconductor substrate; a first conductive layer over the semiconductor substrate; a conductive via passing through the first conductive layer and electrically connected to the first conductive layer; a conductive pad over and in direct contact with the conductive via; a second conductive layer over and spaced apart from the first conductive layer, wherein a first lower portion of the second conductive layer is embedded in the first conductive layer, the first lower portion is a single continuous portion, and the conductive via penetrates into and through the second conductive layer and is electrically insulated from the second conductive layer; a first dielectric layer conformally covering a second lower portion of a sidewall of the second conductive layer, wherein the first dielectric layer is in direct contact with the second lower portion of the sidewall, and the first dielectric layer is a single layer structure; and a third conductive layer over the first dielectric layer, wherein the first dielectric layer is in direct contact with the third conductive layer, the conductive via is electrically connected to the third conductive

layer, the third conductive layer has a top surface, a first upper surface, a second upper surface, a first sidewall, a second sidewall, and a third sidewall, the first upper surface is lower than the top surface and higher than the second upper surface, wherein the top surface, the first upper surface, and the second upper surface face away from the semiconductor substrate, the first sidewall is connected between the top surface and the first upper surface, the second sidewall is connected between the first upper surface and the second upper surface, the third sidewall is connected to the second upper surface, the third conductive layer has a first corner, a second corner, and a third corner, the first corner is between the top surface and the first sidewall, the second corner is between the first upper surface and the second sidewall, the third corner is between the second upper surface and the third sidewall, and the first corner is between the second corner and the conductive via.

2. The chip structure as claimed in claim 1, further comprising: a wiring layer between the semiconductor substrate and the first conductive layer, wherein the wiring layer comprises a conductive line, and the conductive via is over and electrically connected to the first conductive line.

3. The chip structure as claimed in claim 2, wherein the first conductive layer is thinner than the conductive line.

4. The chip structure as claimed in claim 2, wherein the first conductive layer is thinner than the conductive pad.

5. The chip structure as claimed in claim 1, further comprising: a second dielectric layer over the first conductive layer, wherein the second conductive layer is over the second dielectric layer, the second dielectric layer separates the first conductive layer from the second conductive layer, and the conductive via further passes through the second dielectric layer.

6. The chip structure as claimed in claim 5, wherein the second dielectric layer is thinner than the first conductive layer.

7. A chip structure, comprising: a semiconductor substrate; a conductive line over the semiconductor substrate; a first conductive layer over the conductive line, wherein the first conductive layer is thinner than the conductive line, and the first conductive layer has an inner wall and a top surface; a first dielectric layer conformally covering a first lower portion of the inner wall of the first conductive layer, wherein the first dielectric layer is formed of a first single continuous dielectric film; a second conductive layer over the first dielectric layer; a second dielectric layer conformally covering a second lower portion of a sidewall of the second conductive layer, wherein the second dielectric layer is formed of a second single continuous dielectric film, and the second dielectric layer is in direct contact with the first dielectric layer; a third conductive layer over the second dielectric layer and having a conductive film, a first dummy film, and a second dummy film, wherein the conductive film, the first dummy film, the second dummy film are spaced apart and electrically insulated from each other, and a portion of the conductive film is between the first dummy film and the second dummy film; a conductive via passing through the first conductive layer, the second conductive layer, and the conductive film of the third conductive layer and electrically connected to the first conductive layer, the conductive film of the third conductive layer, and the conductive line and electrically insulated from the second conductive layer; and a conductive pad over and in direct contact with the conductive via.

8. The chip structure as claimed in claim 7, wherein the first dummy film, the second dummy film, and the conductive film are made of a same conductive material.

9. The chip structure as claimed in claim 7, further comprising: a bump structure over and in direct contact with the conductive pad.

10. The chip structure as claimed in claim 7, wherein the first dielectric layer is thinner than the first conductive layer.

11. A chip structure, comprising: a semiconductor substrate; a first capacitor electrode over the semiconductor substrate and having an inner wall; a second capacitor electrode over the first

capacitor electrode, wherein the second capacitor electrode is spaced apart from the first capacitor electrode, the inner wall of the first capacitor electrode laterally and continuously surrounds an entirety of a lower portion of the second capacitor electrode, and the lower portion is a single continuous portion; a conductive structure passing through the second capacitor electrode and electrically connected to the second capacitor electrode; a bump structure over and in direct contact with the conductive structure; and a dummy conductive film over the semiconductor substrate and laterally and entirely surrounded by the inner wall of the first capacitor electrode, wherein the second capacitor electrode covers the dummy conductive film, the dummy conductive film is embedded in the second capacitor electrode, the conductive structure further penetrates into and through the dummy conductive film, a first bottom surface of the first capacitor electrode is substantially level with a second bottom surface of the dummy conductive film, and the first bottom surface and the second bottom surface face the semiconductor substrate.

12. The chip structure as claimed in claim 11, wherein the conductive structure is in direct contact with the second capacitor electrode.

13. The chip structure as claimed in claim 12, wherein the conductive structure is in direct contact with the dummy conductive film.

14. The chip structure as claimed in claim 11, wherein the lower portion of the second capacitor electrode has a U-like shape.

15. The chip structure as claimed in claim 11, wherein the dummy conductive film and the first capacitor electrode are made of a same material.

16. The chip structure as claimed in claim 11, further comprising: a dielectric layer conformally and continuously covering a first top surface and the inner wall of the first capacitor electrode and a second top surface and a sidewall of the dummy conductive film, wherein the second capacitor electrode conformally and continuously covers the dielectric layer.

17. The chip structure as claimed in claim 11, wherein the conductive structure is electrically connected to the dummy conductive film.

18. The chip structure as claimed in claim 1, wherein a first distance between the first corner and the conductive via is less than a second distance between the second corner and the conductive via, and the second distance is less than a third distance between the third corner and the conductive via.

19. The chip structure as claimed in claim 7, wherein the conductive film surrounds the entire first dummy film and is located on one side of the second dummy film.

20. The chip structure as claimed in claim 11, wherein the dummy conductive film is between the semiconductor substrate and the second capacitor electrode.

---