

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12397516
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Roberts; Herbert Chidsey et al.

Method for repairing composite components using a support member

Abstract

A method for repairing composite components includes positioning one or more repair fiber plies relative to a repair interface of a composite component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite component. Furthermore, the method includes forming a cavity within the composite component such that the cavity extends through the repair interface. Additionally, the method includes installing a support member within the cavity. In this respect, the support member extends across the butt joint such that a first portion of the support member is positioned within the composite component and a second portion of the support member is positioned within the one or more repair fiber plies.

Inventors: Roberts; Herbert Chidsey (Middletown, OH), Grossman; Theodore Robert (Cincinnati, OH)

Applicant: General Electric Company (Schenectady, NY)

Family ID: 1000008779473

Assignee: General Electric Company (Evendale, OH)

Appl. No.: 17/113257

Filed: December 07, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20220176658 A1	Jun. 09, 2022

Publication Classification

Int. Cl.: B29C73/10 (20060101); B29L31/00 (20060101); B29L31/30 (20060101)

U.S. Cl.:

Field of Classification Search**CPC:** B29C (73/10)**References Cited****U.S. PATENT DOCUMENTS**

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
4916880	12/1989	Westerman, Jr.	29/402.09	B29C 73/04
5448041	12/1994	Benoit	219/638	C03B 23/20
5868886	12/1998	Alston	156/92	B64F 5/40
5876540	12/1998	Pannell	N/A	N/A
5928448	12/1998	Daws	156/92	B23P 6/00
5958166	12/1998	Walters et al.	N/A	N/A
7419556	12/2007	Holland	N/A	N/A
8540909	12/2012	Dan-Jumbo et al.	N/A	N/A
8545650	12/2012	Evens et al.	N/A	N/A
8844108	12/2013	Miller et al.	N/A	N/A
9382017	12/2015	Benthien et al.	N/A	N/A
9387636	12/2015	Takagi et al.	N/A	N/A
9434139	12/2015	Dan-Jumbo	N/A	N/A
9522512	12/2015	Georgeson et al.	N/A	N/A
9993983	12/2017	Nishimura	N/A	N/A
2007/0289692	12/2006	Bogue	156/98	B29C 73/10
2008/0233346	12/2007	Bogue	428/116	B29C 73/10
2008/0263844	12/2007	Stadtlander	29/402.09	B64F 5/40
2011/0318562	12/2010	Dry	428/221	C04B 28/02
2012/0301702	12/2011	Nishimura	29/402.09	B29C 73/04
2016/0137316	12/2015	Shigetomi et al.	N/A	N/A
2017/0089324	12/2016	Sanz Pascual	N/A	N/A
2019/0360346	12/2018	Underwood et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
102009028864	12/2010	DE	B29C 65/564
102010053574	12/2011	DE	B29C 73/10
WO 96/15899	12/1995	WO	N/A
WO-2017081456	12/2016	WO	N/A

OTHER PUBLICATIONS

Machine Translation, Benthien Hermann et al., DE-102010053574-A1, Method for repairing an aircraft structural component, 2012, obtained from Espacenet.com, (Year: 2012). cited by examiner
Machine Translation, Ricardo, DE-102009028864-A1, Transport container has container walls that are made of hard foam, where container walls have breakdown in form of air gap with air gap surfaces opposite to each other, 2011, Espacenet.com. (Year: 2011). cited by examiner
<https://www.aerospacemanufacturinganddesign.com/article/amd0313-repair-structural-composite-parts/> “HOKE” (Year: 2013). cited by examiner

Primary Examiner: Krasnow; Nicholas R

Attorney, Agent or Firm: Dority & Manning, P.A.

Background/Summary

FIELD

(1) The present disclosure generally pertains to methods for repairing components and, more specifically, to methods for securing new composite material to an existing composite component that is worn or damaged.

BACKGROUND

(2) In recent years, the use of non-traditional high temperature materials, such as ceramic matrix composite (CMC) materials, in gas turbine engines has grown dramatically. Specifically, there is strong interest in replacing metal alloy components within the combustion and turbine sections of a gas turbine engine with CMC components. CMC materials can withstand higher operating temperatures than metal alloys. Higher operating temperatures, in turn, increase the efficiency of the gas turbine engine. Moreover, CMC components require less cooling than metallic components. Additionally, CMC materials are lighter than metallic components and may reduce the structural demands on the engine.

(3) However, gas turbine components formed from CMC materials can be quite expensive. In this respect, when a CMC gas turbine component becomes worn or damaged, it may be desirable to repair, rather than replace, the component. As such, methods of repairing CMC components have been developed. Specifically, the worn or damaged portion(s) of a CMC component may be removed and replaced with new CMC material. In such methods, the new CMC material is typically joined to the existing component via a scarf joint. However, when repairing the edges of certain components (e.g., blades), there is not enough material present (e.g., the edge is too thin) to form a scarf joint.

(4) Accordingly, an improved method for repairing composite components would be welcomed in the technology.

BRIEF DESCRIPTION

(5) Aspects and advantages of the invention will be set forth in part in the following description, or may be obvious from the description, or may be learned through practice of the invention.

(6) In one aspect, the present subject matter is directed to a method for repairing composite components. The method includes positioning one or more repair fiber plies relative to a repair interface of a composite component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite component. Furthermore, the method includes forming a cavity within the composite component such that the cavity extends through the repair interface. In addition, the method includes installing a support member within the cavity. In this

respect, the support member extends across the butt joint such that a first portion of the support member is positioned within the composite component and a second portion of the support member is positioned within the one or more repair fiber plies.

(7) In another aspect, the present subject matter is directed to a method for repairing a composite turbomachine component. The method includes preparing a repair interface of a composite turbomachine component by removing worn or damaged composite material. Additionally, the method includes positioning one or more repair fiber plies at the repair interface in a transverse orientation relative to original fiber plies forming the composite turbomachine component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite turbomachine component. Moreover, the method includes forming a cavity within the composite turbomachine component such that the cavity extends through the repair interface. Furthermore, the method includes installing a support member within the cavity. In this respect, the support member extends across the butt joint such that a first portion of the support member is positioned within the composite turbomachine component and a second portion of the support member is positioned within the one or more repair fiber plies.

(8) These and other features, aspects and advantages of the present invention will become better understood with reference to the following description and appended claims. The accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and, together with the description, serve to explain the principles of the invention.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) A full and enabling disclosure of the present invention, including the best mode thereof, directed to one of ordinary skill in the art, is set forth in the specification, which makes reference to the appended figures, in which:

(2) FIG. 1 is a schematic cross-sectional view of one embodiment of a gas turbine engine;

(3) FIG. 2 is a side view of one embodiment of a shroud block of a gas turbine engine;

(4) FIG. 3 is a flow diagram of one embodiment of a method for repairing composite components;

(5) FIG. 4 is a top view of one embodiment of a composite component, particularly illustrating the component prior to repair;

(6) FIG. 5 is top view of the composite component shown in FIG. 4, particularly illustrating a repair interface of the component after preparation for repair;

(7) FIG. 6 is a top view of the composite component shown in FIGS. 4 and 5, particularly illustrating repair fiber plies positioned relative to the repair interface of the component such that a butt joint is formed;

(8) FIG. 7 is a cross-sectional view of the composite component shown in FIGS. 4-6 taken about line 7-7 in FIG. 6, particularly illustrating the repair fiber plies oriented transversely relative to the fiber plies of the component;

(9) FIG. 8 is a top view of the composite component shown in FIGS. 4-7, particularly illustrating holes formed within the repair fiber plies and the composite component; and

(10) FIG. 9 is a top view of the composite component shown in FIGS. 4-7, particularly illustrating a slot formed within the repair fiber plies and the composite component;

(11) FIG. 10 is a top view of the composite component shown in FIGS. 4-8, particularly illustrating a pin positioned within one of the holes formed within the repair fiber plies and the composite component;

(12) FIG. 11 is a top view of the composite component shown in FIGS. 4-7 and 9, particularly illustrating a key or plate positioned within the slot formed within the repair fiber plies and the

composite component;

(13) FIG. 12 is a flow diagram of another embodiment of a method for repairing composite components;

(14) FIG. 13 is a top view of the composite component shown in FIGS. 4 and 5, particularly illustrating holes formed within the composite component;

(15) FIG. 14 is a top view of the composite component shown in FIGS. 4 and 5, particularly illustrating a slot formed within the composite component;

(16) FIG. 15 is a top view of the composite component shown in FIGS. 4, 5, and 13, particularly illustrating pins installed within the formed holes;

(17) FIG. 16 is a top view of the composite component shown in FIGS. 4, 5, and 14, particularly illustrating a plate installed within the formed holes;

(18) FIG. 17 is a top view of the composite component shown in FIGS. 4, 5, 13, and 15, particularly illustrating repair fiber plies positioned relative to the repair interface of the component such that a butt joint is formed; and

(19) FIG. 18 is a top view of the composite component shown in FIGS. 4, 5, 14, and 16, particularly illustrating repair fiber plies positioned relative to the repair interface of the component such that a butt joint is formed.

(20) Repeat use of reference characters in the present specification and drawings is intended to represent the same or analogous features or elements of the present invention.

DETAILED DESCRIPTION

(21) Reference now will be made in detail to exemplary embodiments of the presently disclosed subject matter, one or more examples of which are illustrated in the drawings. Each example is provided by way of explanation and should not be interpreted as limiting the present disclosure. In fact, it will be apparent to those skilled in the art that various modifications and variations can be made in the present disclosure without departing from the scope or spirit of the present disclosure. For instance, features illustrated or described as part of one embodiment can be used with another embodiment to yield a still further embodiment. Thus, it is intended that the present disclosure covers such modifications and variations as come within the scope of the appended claims and their equivalents.

(22) As used herein, the terms “first”, “second”, and “third” may be used interchangeably to distinguish one component from another and are not intended to signify location or importance of the individual components.

(23) Furthermore, the terms “upstream” and “downstream” refer to the relative direction with respect to fluid flow in a fluid pathway. For example, “upstream” refers to the direction from which the fluid flows, and “downstream” refers to the direction to which the fluid flows.

(24) Additionally, the terms “low,” “high,” or their respective comparative degrees (e.g., lower, higher, where applicable) each refer to relative speeds within an engine, unless otherwise specified. For example, a “low-pressure turbine” operates at a pressure generally lower than a “high-pressure turbine.” Alternatively, unless otherwise specified, the aforementioned terms may be understood in their superlative degree. For example, a “low-pressure turbine” may refer to the lowest maximum pressure turbine within a turbine section, and a “high-pressure turbine” may refer to the highest maximum pressure turbine within the turbine section.

(25) In general, the present subject matter is directed to a method for repairing composite components. In several embodiments, the disclosed method may be used to repair various turbomachine components, such as ceramic matrix composite (CMC) gas turbine engine blades, vanes, shroud blocks, liners, and/or the like. More specifically, during operation, a composite component may become worn or damaged. For example, in certain instances, the damaged portion of the composite component may even break off otherwise become separated from the remainder of the composite component. As such, in accordance with the disclosed method, new composite material is formed in place of the worn/damaged portion of the composite component.

(26) The new composite material is joined to the composite component via a butt joint and supported relative thereto via one or more support members, such as a pin(s) or a plate(s). Specifically, in one embodiment, repair fiber plies are positioned relative to a repair interface of the composite component such that a butt joint is formed at the repair interface between the repair fiber plies and the component. Thereafter, one or more cavities are formed within the repair fiber plies and the component such that the cavity(ies) extends through the repair interface. A support member(s) is then installed within the cavity(ies). In another embodiment, one or more cavities are formed within the composite component such that the cavity(ies) extends through the repair interface. A support member is then installed within each cavity. Thereafter, repair fiber plies are pressed over the support member(s), thereby positioning the plies relative to a repair interface such that a butt joint is formed. Regardless of whether positioning the repair fiber plies occurs before or after installing the support member(s), the result is that each support member extends across the butt joint such that a first portion of each support member is positioned within the composite component and a second portion of each support member is positioned within the repair fiber plies.

(27) The use of the support member(s) and the butt joint provide one or more technical advantages. More specifically, as mentioned above, the edges of certain composite components (e.g., turbine blades) do not have enough material to form a scarf joint with the repair fiber plies. In this respect, the disclosed method forms a butt joint between the fiber plies of the composite component and the repair fiber plies, which requires less material than a scarf joint. However, an unsupported butt joint is weak and typically unable to meet the operational requirements of the component. In this respect, the support member(s), such as the pin(s) or the plate(s), support the butt joint between the fiber plies of the component and the repair fiber plies. As such, the support member(s) strengthen the butt joint such that the butt joint is strong enough to support the operational loads of the component.

(28) Referring now to the drawings, FIG. 1 is a schematic cross-sectional view of one embodiment of a gas turbine engine **10**. In the illustrated embodiment, the engine **10** is configured as a high-bypass turbofan engine. However, in alternative embodiments, the engine **10** may be configured as a propfan engine, a turbojet engine, a turboprop engine, a turboshaft gas turbine engine, or any other suitable type of gas turbine engine.

(29) As shown in FIG. 1, the engine **10** defines a longitudinal direction L, a radial direction R, and a circumferential direction C. In general, the longitudinal direction L extends parallel to an axial centerline **12** of the engine **10**, the radial direction R extends orthogonally outward from the axial centerline **12**, and the circumferential direction C extends generally concentrically around the axial centerline **12**.

(30) In general, the engine **10** includes a fan **14**, a low-pressure (LP) spool **16**, and a high pressure (HP) spool **18** at least partially encased by an annular nacelle **20**. More specifically, the fan **14** may include a fan rotor **22** and a plurality of fan blades **24** (one is shown) coupled to the fan rotor **22**. In this respect, the fan blades **24** are spaced apart from each other along the circumferential direction C and extend outward from the fan rotor **22** along the radial direction R. Moreover, the LP and HP spools **16**, **18** are positioned downstream from the fan **14** along the axial centerline **12** (i.e., in the longitudinal direction L). As shown, the LP spool **16** is rotatably coupled to the fan rotor **22**, thereby permitting the LP spool **16** to rotate the fan **14**. Additionally, a plurality of outlet guide vanes or struts **26** spaced apart from each other in the circumferential direction C extend between an outer casing **28** surrounding the LP and HP spools **16**, **18** and the nacelle **20** along the radial direction R. As such, the struts **26** support the nacelle **20** relative to the outer casing **28** such that the outer casing **28** and the nacelle **20** define a bypass airflow passage **30** positioned therebetween.

(31) The outer casing **28** generally surrounds or encases, in serial flow order, a compressor section **32**, a combustion section **34**, a turbine section **36**, and an exhaust section **38**. For example, in some embodiments, the compressor section **32** may include a low-pressure (LP) compressor **40** of the LP spool **16** and a high-pressure (HP) compressor **42** of the HP spool **18** positioned downstream from

the LP compressor **40** along the axial centerline **12**. Each compressor **40, 42** may, in turn, include one or more rows of stator vanes **44** interdigitated with one or more rows of compressor rotor blades **46**. Moreover, in some embodiments, the turbine section **36** includes a high-pressure (HP) turbine **48** of the HP spool **18** and a low-pressure (LP) turbine **50** of the LP spool **16** positioned downstream from the HP turbine **48** along the axial centerline **12**. Each turbine **48, 50** may, in turn, include one or more rows of stator vanes **52** interdigitated with one or more rows of turbine rotor blades **54**.

(32) Additionally, the LP spool **16** includes the low-pressure (LP) shaft **56** and the HP spool **18** includes a high pressure (HP) shaft **58** positioned concentrically around the LP shaft **56**. In such embodiments, the HP shaft **58** rotatably couples the rotor blades **54** of the HP turbine **48** and the rotor blades **46** of the HP compressor **42** such that rotation of the HP turbine rotor blades **54** rotatably drives HP compressor rotor blades **46**. As shown, the LP shaft **56** is directly coupled to the rotor blades **54** of the LP turbine **50** and the rotor blades **46** of the LP compressor **40**. Furthermore, the LP shaft **56** is coupled to the fan **14** via a gearbox **60**. In this respect, the rotation of the LP turbine rotor blades **54** rotatably drives the LP compressor rotor blades **46** and the fan blades **24**.

(33) In several embodiments, the engine **10** may generate thrust to propel an aircraft. More specifically, during operation, air (indicated by arrow **62**) enters an inlet portion **64** of the engine **10**. The fan **14** supplies a first portion (indicated by arrow **66**) of the air **62** to the bypass airflow passage **30** and a second portion (indicated by arrow **68**) of the air **62** to the compressor section **32**. The second portion **68** of the air **62** first flows through the LP compressor **40** in which the rotor blades **46** therein progressively compress the second portion **68** of the air **62**. Next, the second portion **68** of the air **62** flows through the HP compressor **42** in which the rotor blades **46** therein continue progressively compressing the second portion **68** of the air **62**. The compressed second portion **68** of the air **62** is subsequently delivered to the combustion section **34**. In the combustion section **34**, the second portion **68** of the air **62** mixes with fuel and burns to generate high-temperature and high-pressure combustion gases **70**. Thereafter, the combustion gases **70** flow through the HP turbine **48** which the HP turbine rotor blades **54** extract a first portion of kinetic and/or thermal energy therefrom. This energy extraction rotates the HP shaft **58**, thereby driving the HP compressor **42**. The combustion gases **70** then flow through the LP turbine **50** in which the LP turbine rotor blades **54** extract a second portion of kinetic and/or thermal energy therefrom. This energy extraction rotates the LP shaft **56**, thereby driving the LP compressor **40** and the fan **14** via the gearbox **60**. The combustion gases **70** then exit the engine **10** through the exhaust section **38**.

(34) FIG. 2 is a side view of one embodiment of a shroud block **72** of the gas turbine engine **10**. In general, several shroud blocks **72** are circumferentially arranged to form a shroud (not shown) enclosing or otherwise surrounding one of the rows of rotor blades **46** in the compressor section **32** or one of the rows of rotor blades **54** in the turbine section **36**. As shown, the shroud block **72** includes an annular wall **74** extending between an inner surface **76** and an outer surface **78** in the radial direction **R**. The inner surface **76** is, in turn, positioned in close proximity to the tips of the corresponding blades **46, 54** to minimize the leakage of the air/combustion gases **68/70** past the blades **46, 54**. Furthermore, the shroud **72** includes a pair of mounting rails **80** (one is shown). The rails **80** are spaced apart from each other in the longitudinal direction **L** and extend outward from the outer surface **78** of the annular wall **74** in the radial direction **R**. Moreover, each rail **80** defines a pair of mounting holes **82** for coupling the shroud block **72** to the outer casing **28** of the engine **10**. However, in alternative embodiments, the shroud block **72** may have any other suitable configuration.

(35) Additionally, one or more the components of the gas turbine engine **10** may be formed of a composite material, such as ceramic matrix composite (CMC) material or polymer matrix composite (PMC) material. For example, in several embodiments, the compressor vanes **44**, the compressor blades **46**, the turbine vanes **52**, the turbine blades **54**, and shroud blocks **72** may be

formed from CMC materials and the fan blades **24** may be formed from PMC materials. However, in alternative embodiments, any other suitable components of the engine **10** may be formed by composite materials.

(36) The configuration of the gas turbine engine **10** described above and shown in FIGS. **1** and **2** is provided only to place the present subject matter in an exemplary field of use. Thus, the present subject matter may be readily adaptable to any manner of gas turbine engine configuration, including other types of aviation-based gas turbine engines, marine-based gas turbine engines, and/or land-based/industrial gas turbine engines.

(37) FIG. **3** is a flow diagram of one embodiment of a method **100** for repairing composite components. Although FIG. **3** depicts steps performed in a particular order, the disclosed methods are not limited to any particular order or arrangement. As such, the various steps of the disclosed methods can be omitted, rearranged, combined, and/or adapted in various ways without deviating from the scope of the present disclosure.

(38) In general, the various steps of the method **100** will be described below in the context of repairing a composite component **200** as schematically depicted in FIGS. **4-11**. For example, as will be described below, the composite component **200** may correspond to a composite component of the gas turbine engine **10**. However, in alternative embodiments, the composite component **200** may correspond to any other suitable composite component.

(39) FIG. **4** is a perspective view of one embodiment of the composite component **200**. As shown, the composite component **200** includes a repair region **202**. In general, the repair region **202** corresponds to a portion of the component **200** that will be repaired in accordance with the methods disclosed herein. For example, in certain instances, a damaged/worn portion of the component **200** may break off or separate from the remainder of the component **200**. In such instances, at least a portion of the repair region **202** may be devoid of composite material prior to repair. Furthermore, as will be described below, it may be necessary to remove additional material from the repair region **200**, such as when the repair region **202** has an irregular surface **204**, to facilitate repair. As such, the repair region **202** is portion of the component **200** that will be replaced with new composite material. Although the component **200** shown in FIG. **1** only includes one repair region **202**, the component **200** may, in other embodiments, include any other suitable number of repair regions **202**.

(40) Moreover, the composite component **200** may be formed from any suitable composite material. For example, the composite material may be selected from the group consisting of, but not limited to, a ceramic matrix composite (CMC), a polymer matrix composite (PMC), a metal matrix composite (MMC), or a combination thereof. Suitable examples of matrix material for a CMC include, but are not limited to, silicon carbide, aluminum-oxide, silicon oxide, and combinations thereof. Suitable examples of matrix material for a PMC include, but are not limited to, epoxy-based matrices, polyester-based matrices, and combinations thereof. Suitable examples of a matrix material for a MMC include, but are not limited to, aluminum, titanium, and combination thereof. For example, a MMC may be formed from powder metals such as, but not limited to, aluminum powder or titanium powder capable of being melted into a continuous molten liquid metal which can encapsulate fibers present in the assembly, before being cooled into a solid ingot with incased fibers. The resulting MMC is a metal article with increased stiffness, and the metal portion (matrix) is the primary load carrying element.

(41) Referring again to FIG. **3**, at **(102)**, the method **100** includes preparing a repair interface of a composite component for repair. Specifically, in several embodiments, at **(102)**, the worn or damaged material within the repair region **202** that has not already broken off or separated from a remainder of the composite component **200** may be removed from the component **200** via machining, grinding, cutting, and/or the like. For example, in certain instances, as shown in FIG. **4**, the repair region **202** may include an irregular surface **204** unsuitable for joining to the new composite material. In such instances, at **(102)**, material from the component **200** may be removed

to form a suitable repair interface **206**. The repair interface **206** is, in turn, the surface of the component **200** to which the new composite material will be joined. As shown in FIG. 5, upon completion of **(102)**, the worn/damaged material of the repair region **202** has been removed and the repair interface **206** has been formed. In an embodiment, the repair interface **206** forms a regular surface, i.e., a smooth or even surface, such as a planar surface.

(42) Additionally, as shown in FIG. 3, after preparing the repair interface, at **(104)**, the method **100** includes positioning one or more repair fiber plies relative to the repair interface of the composite component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite component. For example, as shown in FIGS. 6 and 7, repair fiber plies **208** are positioned relative to the component **200** such that a butt joint **210** is formed at the repair interface **206** between the repair fiber plies **208** and the component **200**. In this respect, the repair fiber plies **208** are in contact with the repair interface **206** and occupy the space where the worn/damaged material was originally present. As will be described below, a matrix precursor material is provided (e.g., via infiltration or infusion) such that new composite material is formed in the repair region **202**, thereby repairing the component **200**. In this respect, the repair fiber plies **208** correspond to the fiber material of the composite material from which the component **200** is formed.

(43) As specifically shown in FIG. 7, at **(104)**, in several embodiments, the repair fiber plies **208** are oriented transversely relative to the fiber plies **212** of the composite component **200**. Such a transverse orientation strengthens the butt joint **206**, thereby increasing the operational loads that the repaired component **200** can withstand. However, in alternative embodiments, the repair fiber plies **208** may be oriented in any other suitable manner relative to the fiber plies **212** of the composite component **200**.

(44) Furthermore, as shown in FIG. 3, at **(106)**, after positioning the repair ply(ies), the method **100** includes forming a cavity within the composite component such that the cavity extends through the repair interface. For example, as shown in FIG. 8, in one embodiment, after positioning the repair fiber plies **208**, a pair of holes **214** is formed (e.g., via drilling) within the repair fiber plies **208** and the composite component **200** such that the holes **214** extend through the repair interface **206**. In this respect, a first portion of each hole **214** is positioned within the composite component **200** and a second portion of each hole **214** is positioned within the repair region **202**. In another embodiment, as shown in FIG. 9, after positioning the repair fiber plies **208**, a slot **215** is formed (e.g., via milling) within the repair fiber plies **208** and the composite component **200** such that the slot **215** extends through the repair interface **206**. In this respect, a first portion of the slot **215** is positioned within the composite component **200** and a second portion of the slot **215** is positioned within the repair region **202**. However, in alternative embodiments, any other suitable number and/or type of cavity may be formed at **(106)**.

(45) Moreover, as shown in FIG. 3, at **(108)**, the method **100** includes installing a support member within the cavity. Specifically, as shown in FIG. 10, in one embodiment, a pin **216** is installed within each hole **214** such that a first portion **218** of each pin **216** is positioned within the composite component **200** and a second portion **220** of each pin **216** is positioned within the repair fiber plies **208**. As shown in FIG. 11, in another embodiment, a key or plate **217** is installed within the slot **215** such that a first portion **219** of the plate **217** is positioned within the composite component **200** and a second portion **221** of the plate **217** is positioned within the repair fiber plies **208**. As will be described below, the support member(s) (e.g., the pins **216** or the plate **217**) support the repair fiber plies **208** relative to the component **200**, thereby strengthening the butt joint **210**. The support member(s) may be formed from any suitable material, such as a metallic material or a composite material. However, in alternative embodiments, the support member(s) may be configured as any other suitable device or component capable of supporting the repair fiber plies **208** and the component **200** relative to each other in a butt joint connection.

(46) In addition, as shown in FIG. 3, after installing the support member, at **(108)**, the method **100**

includes providing a matrix precursor to the one or more repair fiber plies. More specifically, after the repair fiber plies **208** have been positioned and the pins **216** have been installed, a matrix precursor is supplied or otherwise provided to the repair fiber plies **208**. For example, in one embodiment, the composite component **200** is formed from a ceramic matrix composite (CMC) material. In such an embodiment, at **(108)**, the repair fiber plies **208** are infiltrated (e.g., via melt infiltration) with a suitable infiltrant (e.g., silicon). In another embodiment, the composite component **200** is formed from a polymeric matrix composite (PMC) material. In such an embodiment, (at **108**), the repair fiber plies **208** are infused (e.g., via vacuum infiltration) with a suitable resin. However, in alternative embodiments, the matrix precursor may be provided to the repair fiber plies **208** in any other suitable manner.

(47) In addition, at **(112)**, after providing the matrix material, the method **100** includes heat treating the one or more repair fiber plies. For example, after infiltrating or infusing the repair fiber plies **208**, the plies **208** are heat treated (e.g., in a suitable furnace). After heat treatment at **(112)**, the support member(s) (e.g., the pins **216** or the plate **217**) remain in the composite component **200**. In this respect, the support member(s) support the butt joint **210** between the fiber plies **212** of the component **200** and the repair fiber plies **208**. As such, the support member(s) strengthen the butt joint **210** such that the butt joint **210** is strong enough to support the operational loads of the component **200**.

(48) FIG. **12** is a flow diagram of another embodiment of a method **300** for repairing composite components. As will be described below, the steps of the embodiment of the method **300** shown in FIG. **12** are similar to the steps of the embodiment of the method **100** shown in FIG. **3**. However, some of the steps of the embodiment of the method **300** shown in FIG. **12** are performed in a different order than the embodiment of the method **100** shown in FIG. **3**. In general, the various steps of the method **300** will be described below in the context of repairing a composite component **200** as schematically depicted in FIGS. **13-18** where like reference numerals are used to refer to like features depicted in reference to component **200** of FIGS. **4-11**.

(49) As shown in FIG. **12**, at **(302)**, the method **300** may include preparing a repair interface in the repair region **202** of a composite component **200** for repair as described above in reference to **(102)**.

(50) Additionally, as shown in FIG. **12**, after preparing the repair interface, at **(304)**, the method **300** includes forming a cavity within the composite component such that the cavity extends through the repair interface. For example, as shown in FIG. **13**, in one embodiment, a pair of holes **214** is formed (e.g., via drilling) within the composite component **200** such that the holes **214** extend through the repair interface **206**. As shown in FIG. **14**, in one embodiment, a slot **215** is formed (e.g., via milling) within the composite component **200** such that the slot **215** extends through the repair interface **206**. However, in alternative embodiments, any other suitable number and/or type of cavity may be formed at **(304)**.

(51) Further, as shown in FIG. **12**, at **(306)**, the method **300** includes installing a support member within the cavity. Specifically, as shown in FIG. **15**, in one embodiment, pins **216** are installed within the holes **214** such that a first portion **218** of each pin **216** is positioned within the composite component **200** and a second portion **220** of each pin **216** extends outward from the repair interface **206**. As shown in FIG. **16**, in another embodiment, a key or plate **217** is installed within the slot **215** such that a first portion **219** of the plate **217** is positioned within the composite component **200** and a second portion **221** of the plate **217** extends outward from the repair interface **206**. However, in alternative embodiments, the support member(s) may be configured as any other suitable device or component capable of supporting the repair fiber plies **208** and the component **200** relative to each other in a butt joint connection.

(52) Further, as shown in FIG. **12**, after installing the pin, at **(308)**, the method **300** includes positioning one or more repair fiber plies relative to the repair interface of the composite component such that a butt joint is formed at the repair interface between the one or more repair

fiber plies and the composite component. For example, as shown in FIG. 17, in one embodiment, repair fiber plies **208** are pressed over the pins **216** such that the pins **216** pierce the repair fiber plies **208** and a butt joint **210** is formed at the repair interface **206** with the component **200**. As shown in FIG. 18, in one embodiment, repair fiber plies **208** are pressed over the plate/key **217** such that the plate/key **217** pierces the repair fiber plies **208** and a butt joint **210** is formed at the repair interface **206** with the component **200**. In this respect, the repair fiber plies **208** are in contact with the repair interface **206** and occupy the space where the worn/damaged material was originally present. As shown in FIG. 7, in several embodiments, the repair fiber plies **208** are oriented transversely relative to the fiber plies **212** of the composite component **200**.

(53) In addition, as shown in FIG. 12, at (310), after positioning the repair fiber ply(ies), the method **300** includes providing a matrix precursor to the one or more repair fiber plies as described above.

(54) Further, at (312), after providing the matrix material, the method **100** includes heat treating the one or more repair fiber plies as described above.

(55) In the various embodiments described herein, the support member(s) (e.g., the pins **216** or the plate **217**) may extend completely through the one or more repair fiber plies **208** to an exterior surface of the repaired component, such as depicted in FIGS. 10 and 11. Alternatively, the support member(s) (e.g., the pins **216** or the plate **217**) may extend less than completely through the one or more repair fiber plies **208** so as to be encased within a repaired portion of the composite component, such as depicted in FIGS. 17 and 18. For example, when a plurality of repair fiber plies **208** are pressed over the pins **216** or the plate **217**, the pins **216** or the plate **217** may pierce only one or more but not all of the plurality of repair fiber plies **208**.

(56) The method **100** of FIG. 3 and/or the method **300** of FIG. 12 may apply to repairing composite turbomachine components. Thus, in the embodiments described above, the composite component **200** may be a composite component(s) of the engine **10**. For example, in some embodiments, composite component(s) **200** correspond to a fan blade(s) **24**, a compressor vane(s) **44**, a compressor blade(s) **46**, a turbine vane(s) **52**, a turbine blade(s) **54**, and/or a shroud block(s) **72** of the engine **10**. However, in alternative embodiments, the composite component(s) may correspond to any suitable component(s), such as other component(s) of a turbomachine or component(s) of any other turbomachine.

(57) This written description uses examples to disclose the invention, including the best mode, and also to enable any person skilled in the art to practice the invention, including making and using any devices or systems and performing any incorporated methods. The patentable scope of the invention is defined by the claims, and may include other examples that occur to those skilled in the art. Such other examples are intended to be within the scope of the claims if they include structural elements that do not differ from the literal language of the claims, or if they include equivalent structural elements with insubstantial differences from the literal language of the claims.

(58) Further aspects of the invention are provided by the subject matter of the following clauses:

(59) A method for repairing composite components, the method comprising: positioning one or more repair fiber plies relative to a repair interface of a composite component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite component; forming a cavity within the composite component such that the cavity extends through the repair interface; and installing a support member within the cavity, wherein the support member extends across the butt joint such that a first portion of the support member is positioned within the composite component and a second portion of the support member is positioned within the one or more repair fiber plies.

(60) The method of one or more of these clauses, wherein the support member comprises a pin and the cavity comprises a hole.

(61) The method of one or more of these clauses, wherein the support member comprises a plate and the cavity comprises a slot.

- (62) The method of one or more of these clauses, wherein positioning the one or more repair fiber plies comprises orienting the one or more repair fiber plies transversely relative to a plurality of original fiber plies forming the composite component.
- (63) The method of one or more of these clauses, wherein forming the cavity within the composite component and installing the support member within the cavity are performed before positioning the one or more repair fiber plies relative to the repair interface.
- (64) The method of one or more of these clauses, wherein positioning the one or more repair fiber plies comprises pressing the one or more repair fiber plies over the support member such that the support member pierces the one or more repair fiber plies.
- (65) The method of one or more of these clauses, wherein positioning the one or more repair fiber plies relative to the repair interface is performed before forming the cavity.
- (66) The method of one or more of these clauses, wherein forming the cavity comprises forming the cavity within the one or more repair fiber plies and the composite component such that the cavity extends through the repair interface.
- (67) The method of one or more of these clauses, further comprising: providing a matrix precursor to the one or more repair fiber plies.
- (68) The method of one or more of these clauses, wherein: the composite component is formed from a ceramic matrix composite material; and providing the matrix precursor comprises infiltrating the one or more repair fiber plies with an infiltrant.
- (69) The method of one or more of these clauses, wherein: the composite component is formed from a polymeric matrix composite material; and providing the matrix precursor comprises infusing the one or more repair fiber plies with a resin.
- (70) The method of one or more of these clauses, further comprising: after providing the matrix precursor, heat treating the one or more repair fiber plies.
- (71) The method of one or more of these clauses, wherein the support member remains in the composite component after heat treating.
- (72) The method one or more of these clauses, wherein the support member is formed from a metallic material or a composite material.
- (73) The method of one or more of these clauses, wherein the composite component is a turbomachine component.
- (74) A method for repairing a composite turbomachine component, the method comprising: preparing a repair interface of a composite turbomachine component by removing worn or damaged composite material; positioning one or more repair fiber plies at the repair interface in a transverse orientation relative to original fiber plies forming the composite turbomachine component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite turbomachine component; forming a cavity within the composite turbomachine component such that the cavity extends through the repair interface; and installing a support member within the cavity, wherein the support member extends across the butt joint such that a first portion of the support member is positioned within the composite turbomachine component and a second portion of the support member is positioned within the one or more repair fiber plies.
- (75) The method of one or more of these clauses, wherein forming the cavity within the composite turbomachine component and installing the support member within the cavity are performed before positioning the one or more repair fiber plies the repair interface.
- (76) The method of one or more of these clauses, wherein positioning the one or more repair fiber plies comprises pressing the one or more repair fiber plies over the support member such that the support member pierces the one or more repair fiber plies.
- (77) The method of one or more of these clauses, wherein the one or more repair fiber plies comprises a plurality of repair fiber plies, and wherein the support member pierces less than all of the plurality of repair fiber plies such that the support member is encased within a repaired portion

of the composite turbomachine component.

(78) The method of one or more of these clauses, wherein the composite turbomachine component is formed from a ceramic matrix composite material, the method further comprising: infiltrating the one or more repair fiber plies with an infiltrant; and heat treating the one or more repair fiber plies to form a repaired composite turbomachine component.

(79) The method of one or more of these clauses, wherein positioning the one or more repair fiber plies comprises pressing the one or more repair fiber plies over the support member such that the support member pierces the one or more repair fiber plies.

Claims

1. A method for repairing composite components, the method comprising: removing worn or damaged composite material from a composite component to form a repair interface extending from a first side of the composite component to a second side of the composite component opposite the first side; positioning one or more repair fiber plies relative to the repair interface from the first side to the second side such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite component; after removing the worn or damaged composite material, forming a blind hole or a blind slot within the composite component such that the blind hole or the blind slot extends through the repair interface and into the composite component; and installing a support member within the blind hole or the blind slot, wherein the support member extends across the butt joint such that a first portion of the support member is positioned within the composite component and a second portion of the support member is positioned within the one or more repair fiber plies.

2. The method of claim 1, wherein the support member comprises a pin and the blind hole or the blind slot comprises the blind hole.

3. The method of claim 1, wherein the support member comprises a plate and the blind hole or the blind slot comprises the blind slot.

4. The method of claim 1, wherein positioning the one or more repair fiber plies comprises orienting the one or more repair fiber plies transversely relative to a plurality of original fiber plies forming the composite component.

5. The method of claim 1, wherein forming the blind hole or the blind slot within the composite component comprises installing the support member within the blind hole or the blind slot before positioning the one or more repair fiber plies relative to the repair interface; and installing the support member comprises installing the support member within the blind hole or the blind slot before positioning the one or more repair fiber plies relative to the repair interface.

6. The method of claim 5, wherein positioning the one or more repair fiber plies comprises pressing the one or more repair fiber plies over the support member such that the support member pierces the one or more repair fiber plies.

7. The method of claim 1, wherein positioning the one or more repair fiber plies relative to the repair interface is performed before forming the blind hole or the blind slot.

8. The method of claim 7, wherein forming the blind hole or the blind slot comprises forming the blind hole or the blind slot within the one or more repair fiber plies and the composite component such that the blind hole or the blind slot extends through the repair interface.

9. The method of claim 1, further comprising: providing a matrix precursor to the one or more repair fiber plies.

10. The method of claim 9, wherein: the composite component is formed from a ceramic matrix composite material; and providing the matrix precursor comprises infiltrating the one or more repair fiber plies with an infiltrant.

11. The method of claim 9, wherein: the composite component is formed from a polymeric matrix composite material; and providing the matrix precursor comprises infusing the one or more repair

fiber plies with a resin.

12. The method of claim 9, further comprising: after providing the matrix precursor, heat treating the one or more repair fiber plies.

13. The method of claim 12, wherein the support member remains in the composite component after heat treating.

14. The method of claim 1, wherein the support member is formed from a metallic material or a composite material.

15. The method of claim 1, wherein the composite component is a turbomachine component.

16. A method for repairing a composite turbomachine component, the method comprising: removing worn or damaged composite material from a composite turbomachine component to form a repair interface extending from a first side of the composite turbomachine component to a second side of the composite turbomachine component opposite the first side; positioning one or more repair fiber plies at the repair interface from the first side to the second side in a transverse orientation relative to original fiber plies forming the composite turbomachine component such that a butt joint is formed at the repair interface between the one or more repair fiber plies and the composite turbomachine component; after the worn or damaged composite material is removed, forming a blind hole or a blind slot within the composite turbomachine component such that the blind hole or the blind slot extends through the repair interface and into the composite turbomachine component; and installing a support member within the blind hole or the blind slot, wherein the support member extends across the butt joint such that a first portion of the support member is positioned within the composite turbomachine component and a second portion of the support member is positioned within the one or more repair fiber plies.

17. The method of claim 16, wherein forming the blind hole or the blind slot within the composite turbomachine component and installing the support member within the blind hole or the blind slot are performed before positioning the one or more repair fiber plies the repair interface.

18. The method of claim 17, wherein positioning the one or more repair fiber plies comprises pressing the one or more repair fiber plies over the support member such that the support member pierces the one or more repair fiber plies.

19. The method of claim 18, wherein the one or more repair fiber plies comprises a plurality of repair fiber plies, and wherein the support member pierces less than all of the plurality of repair fiber plies such that the support member is encased within a repaired portion of the composite turbomachine component.

20. The method of claim 16, wherein the composite turbomachine component is formed from a ceramic matrix composite material, the method further comprising: infiltrating the one or more repair fiber plies with an infiltrant; and heat treating the one or more repair fiber plies to form a repaired composite turbomachine component.
