

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12402867
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Do; Hiep et al.

Hemostatic biopsy tract article

Abstract

A hemostatic biopsy tract article includes a bioresorbable body having a microporous structure. The bioresorbable body is formed by a mixture that includes a bioabsorbable hemostatic powder, a hydrolyzed starch, hyaluronic acid, and carboxymethylcellulose. Optionally, a marker element may be coupled to the bioresorbable body, wherein the marker element is formed from a material that is imageable under at least one imaging modality.

Inventors:	Do; Hiep (Chandler, AZ), Addison; Jordan (Gilbert, AZ)
Applicant:	C.R. Bard, Inc. (Franklin Lakes, NJ)
Family ID:	65635832
Assignee:	C.R. Bard, Inc. (Murray Hill, NJ)
Appl. No.:	17/428797
Filed (or PCT Filed):	February 15, 2019
PCT No.:	PCT/US2019/018292
PCT Pub. No.:	WO2020/167319
PCT Pub. Date:	August 20, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20220000459 A1	Jan. 06, 2022

Publication Classification

Int. Cl.: **A61B90/00** (20160101); **A61B10/02** (20060101); **A61L31/04** (20060101); **A61L31/14** (20060101); **C08L1/28** (20060101); **C08L3/04** (20060101); **C08L5/08** (20060101)

U.S. Cl.:

CPC **A61B10/0275** (20130101); **A61B90/39** (20160201); **A61L31/041** (20130101);
A61L31/146 (20130101); **A61L31/148** (20130101); **C08L1/286** (20130101); **C08L3/04**
(20130101); **C08L5/08** (20130101); A61B2090/3908 (20160201); A61L2400/04
(20130101)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6056970	12/1999	Greenawalt et al.	N/A	N/A
6060461	12/1999	Drake	N/A	N/A
6270464	12/2000	Fulton et al.	N/A	N/A
6356782	12/2001	Sirimanne et al.	N/A	N/A
6394965	12/2001	Klein	N/A	N/A
6846320	12/2004	Ashby et al.	N/A	N/A
7329414	12/2007	Fisher et al.	N/A	N/A
7744852	12/2009	Chernomorsky et al.	N/A	N/A
8320993	12/2011	Sirimanne et al.	N/A	N/A
8401622	12/2012	Talpade et al.	N/A	N/A
8880154	12/2013	Jones et al.	N/A	N/A
9044162	12/2014	Jones et al.	N/A	N/A
9149341	12/2014	Jones et al.	N/A	N/A
9327061	12/2015	Govil et al.	N/A	N/A
9801688	12/2016	Jones et al.	N/A	N/A
9820824	12/2016	Jones et al.	N/A	N/A
2002/0016612	12/2001	Ashby	606/213	A61B 17/0057
2002/0035324	12/2001	Sirimanne et al.	N/A	N/A
2005/0142161	12/2004	Freeman et al.	N/A	N/A
2007/0065484	12/2006	Chudzik et al.	N/A	N/A
2007/0086958	12/2006	Drake et al.	N/A	N/A
2007/0087061	12/2006	Drake et al.	N/A	N/A
2009/0062233	12/2008	Ji	N/A	N/A
2010/0082102	12/2009	Govil et al.	N/A	N/A
2010/0179589	12/2009	Roorda et al.	N/A	N/A
2011/0144661	12/2010	Houser et al.	N/A	N/A
2012/0143243	12/2011	Hill et al.	N/A	N/A
2013/0245680	12/2012	Sargeant et al.	N/A	N/A
2014/0171385	12/2013	Burbank et al.	N/A	N/A
2015/0119907	12/2014	Fenton et al.	N/A	N/A
2015/0289861	12/2014	Macphee et al.	N/A	N/A
2016/0015475	12/2015	Jones et al.	N/A	N/A
2017/0216499	12/2016	Kaplan	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
101001649	12/2006	CN	N/A
101485897	12/2008	CN	N/A
101977561	12/2010	CN	N/A
102056564	12/2010	CN	N/A
103687631	12/2013	CN	N/A
104353130	12/2014	CN	N/A
104665897	12/2014	CN	N/A
104888264	12/2014	CN	N/A
204683720	12/2014	CN	N/A
105194712	12/2014	CN	N/A
2281861	12/1992	GB	N/A
2002513645	12/2001	JP	N/A
2009508653	12/2008	JP	N/A
2006005340	12/2005	WO	N/A
2009091549	12/2008	WO	N/A
2009105177	12/2008	WO	N/A
2009134314	12/2008	WO	N/A
2013003045	12/2012	WO	N/A

OTHER PUBLICATIONS

Chinese Office Action and Search Report dated Mar. 22, 2022 pertaining to Chinese patent application 201980092012.2. cited by applicant

Chinese Second Office Action and Search Report dated Nov. 18, 2022, pertaining to Chinese patent application 201980092012.2. cited by applicant

Japanese Office Action dated Nov. 28, 2022, pertaining to Japanese patent application 2021-547357. cited by applicant

Primary Examiner: Babson; Nicole P

Attorney, Agent or Firm: DINSMORE & SHOHL LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

(1) This application is a U.S. national phase of International Application No. PCT/US2019/018292, filed Feb. 15, 2019, which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

(2) The present invention relates a biopsy article for use in biopsy procedures, and, more particularly, to a biopsy tract article having hemostatic properties.

BACKGROUND ART

(3) A stereotactic biopsy procedure is performed by inserting a biopsy probe, e.g., needle, into a patient to form a tract to the biopsy site, where the biopsy probe collects one or more biopsy samples and forms a cavity as a result of tissue removal. Such a biopsy procedure typically results in significant bleeding at the tract, which may include the biopsy cavity, well after the biopsy has been completed. Also, after most biopsies, a tissue marker is deployed at the biopsy site to mark the location of the biopsy site. The tissue marker is configured to be visible under one or more imaging

modalities, such as for example, ultrasound, MRI and X-ray.

(4) What is needed in the art is a hemostatic biopsy tract article that may serve as a hemostatic tract plug, and which optionally may carry a tissue marker so as to both mark the biopsy site and effectively control bleeding at the biopsy site.

SUMMARY OF INVENTION

(5) The present invention provides a hemostatic biopsy tract article that may serve as a hemostatic tract plug, and which optionally may carry a tissue marker so as to both mark the biopsy site and effectively control bleeding at the biopsy site.

(6) The invention in one form is directed to a hemostatic biopsy tract article. The hemostatic biopsy tract article includes a bioresorbable body having a microporous structure. The bioresorbable body is formed by a mixture that includes a bioabsorbable hemostatic powder, a hydrolyzed starch, hyaluronic acid, and carboxymethylcellulose. Optionally, a marker element may be coupled to the bioresorbable body, wherein the marker element is formed from a material that is imageable under at least one imaging modality.

(7) One advantage of the invention is that the bioresorbable body instantly dehydrates and gels blood upon contact with blood by the effect of its hydrophilic materials and microporous structure.

Description

BRIEF DESCRIPTION OF DRAWINGS

(1) The above-mentioned and other features and advantages of this invention, and the manner of attaining them, will become more apparent and the invention will be better understood by reference to the following description of embodiments of the invention taken in conjunction with the accompanying drawings, wherein:

(2) FIG. 1 is a side view of a hemostatic biopsy tract article having a bioresorbable body with a microporous structure.

(3) FIG. 2 is a side view of an introducer device for carrying and delivering the hemostatic biopsy tract article of FIG. 1.

(4) FIG. 3 is a section view of a distal portion of the introducer device of FIG. 2 taken along line 3-3 of FIG. 2.

(5) FIG. 4A is a side view of the hemostatic biopsy tract article having a tissue marker attached to the bioresorbable body.

(6) FIG. 4B is a side view of the hemostatic biopsy tract article having a tissue marker contained in the bioresorbable body.

(7) FIG. 5 is a side view of another embodiment of a hemostatic biopsy tract article that includes a bioresorbable body having a first body segment separated from a second body segment to define a void that carries a marker element, with the void being encapsulated by a bioresorbable sleeve.

(8) Corresponding reference characters indicate corresponding parts throughout the several views. The exemplifications set out herein illustrate at least one embodiment of the invention, and such exemplifications are not to be construed as limiting the scope of the invention in any manner.

DESCRIPTION OF EMBODIMENTS

(9) Referring now to the drawings, and more particularly to FIG. 1, there is shown a hemostatic biopsy tract article **10** in accordance with the present invention.

(10) Referring also to FIG. 2, hemostatic biopsy tract article **10** is designed to be carried by, and expelled from, an introducer device **12**. In the present embodiment, hemostatic biopsy tract article **10** has an elongate cylindrical shape, although it is contemplated that other shapes may be selected, for example, based on the application for which hemostatic biopsy tract article **10** is to be used. Introducer device **12** includes a handle body **14**, a plunger **16**, and a cannula **18**. In the present embodiment, handle body **14** is molded to cannula **18**.

(11) Referring also to FIG. 3, cannula **18** includes a distal end **18-1** and a lumen **18-2**. Lumen **18-2** distally terminates at distal end **18-1** to define a delivery port **18-3** associated with lumen **18-2**. Plunger **16** includes a plunger head **16-1** and a plunger shaft **16-2** that extends from plunger head **16-1**. A distal portion **16-3** of plunger shaft **16-2** of plunger **16** is slidably received in lumen **18-2** of cannula **18**. Hemostatic biopsy tract article **10** is positioned in lumen **18-2** of cannula **18** distal to distal portion **16-3** of plunger **16**.

(12) By depressing plunger head **16-1** in a distal direction **20**, plunger shaft **16-2** moves in distal direction **20** so as to expel hemostatic biopsy tract article **10** from delivery port **18-3** of cannula **18**.

(13) Those skilled in the art will recognize that the distal end **18-1** of cannula **18** may have a configuration other than the beveled tip configuration as shown. For example, it is contemplated that distal end **18-1** may be blunt, rounded, symmetrically pointed, asymmetrically pointed, etc. Also, as an alternative to delivery port **18-3** being located at distal end **18-1** of cannula **18**, it is contemplated that delivery port **18-3** may be formed in the side wall of cannula **18** to facilitate a side delivery of hemostatic biopsy tract article **10** from cannula **18**.

(14) Hemostatic biopsy tract article **10** is configured such that bioresorbable body **10-1** is bioresorbable, hemostatic, and has a microporous structure. In the present embodiment, bioresorbable body **10-1** is formed by a mixture, e.g., a solution, which includes a bioabsorbable hemostatic powder, a hydrolyzed starch, hyaluronic acid, and carboxymethylcellulose. Each of the bioabsorbable hemostatic powder, the hydrolyzed starch, the hyaluronic acid, and the carboxymethylcellulose is a hydrophilic material, and thus, in the present embodiment, bioresorbable body **10-1** is formed using four different hydrophilic materials.

(15) The bioabsorbable hemostatic powder is a plant-based starch powder of a different starch material from that of the hydrolyzed starch. The bioabsorbable hemostatic powder may be, for example, an unhydrolyzed starch. In one form, the bioabsorbable hemostatic powder is commercially available under the tradename, Arista[™]) from C. R. Bard, Inc. (See, e.g., U.S. Pat. No. 6,060,461). The Arista brand starch is an unhydrolyzed starch (plant-based) that comprises of large number of glucose units. In contrast to the Arista brand starch, the hydrolyzed starch contains shorter glucose units (e.g. monosaccharides, disaccharides or trisaccharides).

(16) Hydrolyzed starch consists of smaller saccharides molecules than an initial starch. Starch is a polymeric carbohydrate consisting of a large number of glucose units joined by glycoside bonds. Whenever starch (polysaccharides) molecules undergo hydrolysis, it forms either monosaccharides, disaccharides or trisaccharides.

(17) Hyaluronic acid is an anionic, nonsulfated glycosaminoglycan, which are long unbranched polysaccharides consisting of a repeating disaccharide unit.

(18) Carboxymethylcellulose (CMC) is a cellulose derivative with carboxymethyl groups bound to some of the hydroxyl groups of the glucopyranose monomers that make up the cellulose backbone.

(19) Where the mixture is a solution containing water, e.g., distilled water, the mixture is lyophilized or compressed to remove the water and form bioresorbable body **10-1**. In the present embodiment, no other ingredients are added in this solution. However, it is contemplated that drugs or growth factors can be incorporated in the solution to generate foam that can deliver bioactive components, if desired.

(20) In one example, to achieve the microporous structure having hemostatic and bioresorbable characteristics of the present invention, a ratio of hyaluronic acid to carboxymethylcellulose is in a range of 1:1 to 4:1, and a ratio of the bioabsorbable hemostatic powder to the hydrolyzed starch is in a range of 1:1 to 3:1. It has been observed that a pore size of bioresorbable body **10-1** may be increased by increasing the ratio of hyaluronic acid to carboxymethylcellulose. Conversely, a pore size of the bioresorbable body **10-1** may be decreased by decreasing the ratio of hyaluronic acid to carboxymethylcellulose.

(21) In one embodiment, hemostatic biopsy tract article **10** is formed from a solution that includes the bioabsorbable hemostatic powder (4% to 7% by weight/volume), the hydrolyzed starch (2% to

4% by weight/volume), the hyaluronic acid (0.3% to 1.3% by weight/volume), and the carboxymethylcellulose (0.3% to 1.3% by weight/volume). The estimated overall pore size range is from 20 nanometers to as large as 5 microns.

(22) A specific example follows below.

(23) EXAMPLE: In the present example, a bioresorbable body having a microporous structure in accordance with the present invention is formed by making a solution that is formed by dissolving in distilled water: bioabsorbable hemostatic powder, e.g. Arista brand starch powder, (5% by weight/volume), hydrolyzed starch (4% by weight/volume), hyaluronic acid (0.313% by weight/volume), and carboxymethylcellulose (0.626% by weight/volume). The solution is mixed for 15 minutes or until all particles are dissolved, and is then poured into an open-top container which is then placed onto a pre-cooled shelf, and the microporous foam is formed by removing water by a sublimation process or freeze drying process (e.g., the entire process takes about 24 hours). The pore size of the microporous foam of this example is in a range of 20 nanometers to about 5 microns.

(24) Advantageously, bioresorbable body **10-1** of hemostatic biopsy tract article **10** instantly dehydrates and gels blood upon contact with blood by the effect of the hydrophilic materials and microporous structure. Also, hemostatic biopsy tract article **10** is completely resorbed over a period of time, with the bioabsorbable hemostatic powder being resorbed within 24 to 48 hours of amylases. Again, the bioabsorbable hemostatic powder is a plant-based starch powder of a different starch material from that of the hydrolyzed starch.

(25) It is contemplated that bioresorbable body **10-1** of hemostatic biopsy tract article **10** may be placed into any biopsy tract to achieve hemostasis following a biopsy. Such biopsies may include, for example, a breast biopsy or an organ biopsy, such as for example, a liver or renal biopsy. Further, it is contemplated that lung biopsies may also be embolized with bioresorbable body **10-1** of hemostatic biopsy tract article **10** to form a blood clot at the pleural surfaces and prevent a pneumothorax and promote tissue re-modeling of the lung parenchyma once a blood clot is formed.

(26) Referring to the embodiments of FIGS. **4A** and **4B**, hemostatic biopsy tract article **10** may be adapted to include a tissue marker formed from a material that is imageable under at least one imaging modality, e.g., x-ray, MRI, or ultrasound.

(27) For example, as depicted in FIG. **4A**, hemostatic biopsy tract article **10** may be adapted to include a marker element **22** that is coupled to bioresorbable body **10-1**. Marker element **22** is formed from a material that is imageable under at least one imaging modality, e.g., x-ray, MRI, or ultrasound. For example, where the desired imaging modality is x-ray or MRI, marker element **22** may be formed from stainless steel or titanium. Where the desired imaging modality is ultrasound, marker element **22** may be formed to include reflective surfaces. In the present embodiment depicted in FIG. **4A**, marker element **22** is an exterior band attached to an exterior of bioresorbable body **10-1**.

(28) In the example depicted in FIG. **4B**, hemostatic biopsy tract article **10** may be adapted to contain a marker element **24**, which in turn is coupled to bioresorbable body **10-1** by being contained within bioresorbable body **10-1**. Marker element **24** is formed from a material that is imageable under at least one imaging modality, e.g., x-ray, MRI, or ultrasound. For example, where the desired imaging modality is x-ray or MRI, marker element **24** may be formed from stainless steel or titanium. Where the desired imaging modality is ultrasound, marker element **24** may be formed to include reflective surfaces. In the present embodiment depicted in FIG. **4B**, marker element **24** has a ribbon shape, but it is to be recognized that other shapes of marker element **24**, e.g., ring, flat, coil, loop, hook, polygonal, spherical, elliptical, star, ribbon, a combination, etc., may be utilized based on the medical application or user preference.

(29) While in the embodiments set forth above, bioresorbable body **10-1** of hemostatic biopsy tract article **10** is depicted as having an elongate cylindrical shape, it is contemplated that other shapes may be selected, for example, based on the application for which hemostatic biopsy tract article **10**

is to be used. For example, it is contemplated that bioresorbable body **10-1** of hemostatic biopsy tract article **10** could also be a rolled flat sheet, or multiple flat sheets, and may include a radiopaque or other imageable marker element embedded in the sheet or between sheets.

(30) FIG. 5 shows an embodiment of a hemostatic biopsy tract article **100**, in accordance with another embodiment of the invention. Hemostatic biopsy tract article **100** may be used to mark a biopsy cavity and/or tract, such as for example, a breast biopsy cavity where tissue samples have been removed.

(31) Hemostatic biopsy tract article **100** includes a bioresorbable body **102**, a bioresorbable sleeve **104**, a void **106**, and a marker element **108**. In the present embodiment, hemostatic biopsy tract article **10** has an elongate cylindrical shape, and also may be carried and delivered by an introducer device, such as introducer device **12** shown in FIG. 2.

(32) Bioresorbable body **102** includes a first body segment **102-1** and a second body segment **102-2**. First body segment **102-1** and a second body segment **102-2** are arranged along a longitudinal axis **110**. First body segment **102-1** is spaced a distance **112** from second body segment **102-2** along longitudinal axis **110** to form the void **106** between first body segment **102-1** and second body segment **102-2**. Marker element **108** is positioned in void **106** between first body segment **102-1** and second body segment **102-2**. Bioresorbable sleeve **104** encapsulates void **106** to contain marker element **108**, and bioresorbable sleeve **104** connects, e.g., by a friction fit or biocompatible adhesive, to each of first body segment **102-1** and second body segment **102-2**.

(33) Bioresorbable body **102** has the same chemical composition as that of bioresorbable body **10-1** described above. Accordingly, each of first body segment **102-1** and a second body segment **102-2** also has the same chemical composition as that of bioresorbable body **10-1** described above. First body segment **102-1** and a second body segment **102-2** may be formed individually, or separated from the same base bioresorbable body, such as for example, by dividing bioresorbable body **10-1** into two body segments.

(34) Bioresorbable sleeve **104** may have the same chemical composition as that of bioresorbable body **10-1**, described above, or alternatively, may be a tube formed from another type of bioresorbable material.

(35) Void **106** may be an air space, or alternatively, may be filled with a biocompatible fluid, such as saline or an MRI contrast agent.

(36) Marker element **108** is formed from a material that is imageable under at least one imaging modality, e.g., x-ray, MRI, or ultrasound. Marker element **108** is shown schematically as a rectangle, but may be any suitable shape as determined or desired for a particular purpose. For example, the shape of marker element **108** may be a ring, flat, coil, loop, hook, polygonal, spherical, elliptical, star, ribbon, a combination, etc. Where the desired imaging modality is x-ray or MRI, marker element **108** may be formed from stainless steel or titanium. Where the desired imaging modality is ultrasound, marker element **108** may be formed to include reflective surfaces. It is noted that void **106** may itself provide ultrasound and MRI contrast. Also, it is contemplated that marker element **108** may itself be a plurality of individual marker elements.

(37) As used herein, the terms “connected” or “attached” mean a direct or indirect affixation of one component to another component. The term “about”, and other words of degree, are relative modifiers intended to indicate permissible variation from the characteristic so modified.

(38) The following items also relate to the invention:

(39) A hemostatic biopsy tract article includes a bioresorbable body having a microporous structure. The bioresorbable body may be formed by a mixture that includes a bioabsorbable hemostatic powder, a hydrolyzed starch, hyaluronic acid, and carboxymethylcellulose.

(40) Optionally, a ratio of hyaluronic acid to carboxymethylcellulose may be in a range of 1:1 to 4:1.

(41) Optionally, a ratio of the bioabsorbable hemostatic powder to the hydrolyzed starch may be in a range of 1:1 to 3:1.

- (42) A pore size of the bioresorbable body may be increased by increasing the ratio of hyaluronic acid to carboxymethylcellulose and/or the pore size is in a range of 20 nanometers to 5 microns.
- (43) A pore size of the bioresorbable body may be decreased by decreasing the ratio of hyaluronic acid to carboxymethylcellulose and/or the pore size is in a range of 20 nanometers to 5 microns.
- (44) Optionally, the mixture may be a solution containing water, and wherein the mixture may be lyophilized or compressed to remove the water and form the bioresorbable body.
- (45) Optionally, the mixture may be a solution that includes the bioabsorbable hemostatic powder (4% to 7% by weight/volume), the hydrolyzed starch (2% to 4% by weight/volume), the hyaluronic acid (0.3% to 1.3% by weight/volume), and the carboxymethylcellulose (0.3% to 1.3% by weight/volume).
- (46) In at least one embodiment, the bioresorbable body is configured such that it instantly dehydrates and gels blood upon contact with blood.
- (47) In at least one embodiment, the bioresorbable body is configured such that it is completely resorbed over a period of time.
- (48) Optionally, the bioabsorbable hemostatic powder may be a plant-based starch powder, and/or is of a different starch material than the hydrolyzed starch.
- (49) Optionally, a marker element may be coupled to the bioresorbable body. The marker element may be formed from a material that is imageable under at least one imaging modality.
- (50) Optionally, the marker element may be attached to the bioresorbable body.
- (51) Optionally, alternatively or additionally, the marker element may be contained within the bioresorbable body.
- (52) In another optional arrangement, the bioresorbable body may have a longitudinal axis, a first body segment, and a second body segment, wherein the first body segment is spaced from the second body segment along the longitudinal axis to form a void between the first body segment and the second body segment. Optionally, the marker element is positioned in the void between the first body segment and the second body segment. A bioresorbable sleeve may encapsulate the void and connect to each of the first body segment and the second body segment.
- (53) While this invention has been described with respect to at least one embodiment, the present invention can be further modified within the spirit and scope of this disclosure. This application is therefore intended to cover any variations, uses, or adaptations of the invention using its general principles. Further, this application is intended to cover such departures from the present disclosure as come within known or customary practice in the art to which this invention pertains and which fall within the limits of the appended claims.

Claims

1. A hemostatic biopsy tract article, comprising a bioresorbable body having a microporous structure, the bioresorbable body being formed by a mixture that includes a bioabsorbable hemostatic powder in an amount of 4% to 7% by weight/volume, wherein the bioresorbable hemostatic powder is an unhydrolyzed, plant-based starch, a hydrolyzed starch in an amount of 2% to 4% by weight/volume, hyaluronic acid in an amount of 0.3% to 1.3% by weight/volume, and carboxymethylcellulose in an amount of 0.3% to 1.3% by weight/volume and water, wherein the microporous structure has a pore size from 20 nanometers to 5 microns, wherein the microporous structure is formed by removing water by a sublimation or freeze-drying process.
2. The hemostatic biopsy tract article according to claim 1, wherein a ratio of hyaluronic acid to carboxymethylcellulose is in a range of 1:1 to 4:1.
3. The hemostatic biopsy tract article according to claim 1, wherein a ratio of the bioabsorbable hemostatic powder to the hydrolyzed starch is in a range of 1:1 to 3:1.
4. The hemostatic biopsy tract article according to claim 2, wherein a ratio of the bioabsorbable hemostatic powder to the hydrolyzed starch is in a range of 1:1 to 3:1.

5. The hemostatic biopsy tract article according to claim 1, wherein the pore size of the bioresorbable body is increased by increasing a ratio of hyaluronic acid to carboxymethylcellulose.
 6. The hemostatic biopsy tract article according to claim 1, wherein the pore size of the bioresorbable body is decreased by decreasing a ratio of hyaluronic acid to carboxymethylcellulose.
 7. The hemostatic biopsy tract article according to claim 2, wherein the pore size of the bioresorbable body is increased by increasing the ratio of hyaluronic acid to carboxymethylcellulose.
 8. The hemostatic biopsy tract article according to claim 2, wherein the pore size of the bioresorbable body is decreased by decreasing the ratio of hyaluronic acid to carboxymethylcellulose.
 9. The hemostatic biopsy tract article according to claim 1, wherein the bioresorbable body instantly dehydrates and gels blood upon contact with blood.
 10. The hemostatic biopsy tract article according to claim 2, wherein the bioresorbable body instantly dehydrates and gels blood upon contact with blood.
 11. The hemostatic biopsy tract article according to claim 1, wherein the bioresorbable body is completely resorbed over a period of time.
 12. The hemostatic biopsy tract article according to claim 1, comprising a marker element coupled to the bioresorbable body, the marker element being formed from a material that is imageable under at least one imaging modality.
 13. The hemostatic biopsy tract article according to claim 12, wherein the marker element is attached to the bioresorbable body.
 14. The hemostatic biopsy tract article according to claim 12, wherein the marker element is contained within the bioresorbable body.
 15. The hemostatic biopsy tract article according to claim 12, wherein: the bioresorbable body has a longitudinal axis, a first body segment, and a second body segment, the first body segment being spaced from the second body segment along the longitudinal axis to form a void between the first body segment and the second body segment, the marker element being positioned in the void between the first body segment and the second body segment, and further comprising: a bioresorbable sleeve that encapsulates the void and connects to each of the first body segment and the second body segment.
-