

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12405412

Kind Code

B2

Date of Patent

September 02, 2025

Inventor(s)

Mu; Cheng-Tang et al.

Infrared band pass filter having Si:NH layers with refraction index greater than 3.5

Abstract

The present disclosure relates to an infrared band pass filter, which comprises a first multilayer film. The first multilayer film including a plurality of Si:NH layers and a low refraction index layer. The plurality of low refraction index layers are stacked with Si:NH layers alternatively; wherein the difference between the refraction index of Si:NH layer and the refraction index of the low refraction index layer is greater than 0.5. The infrared band pass filter has a pass band in a wavelength range of 800 nm and 1100 nm, and when the incident angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted less than 12 nm, and the infrared band pass filter of the present disclosure can be used to enhance the 3D image resolution when applied to a 3D imaging system.

Inventors: Mu; Cheng-Tang (Taoyuan, TW), Su; Yu-Ching (Taoyuan, TW)

Applicant: Platinum Optics Technology Inc. (Taoyuan, TW)

Family ID: 65805121

Assignee: Platinum Optics Technology Inc. (Taoyuan, TW)

Appl. No.: 18/331075

Filed: June 07, 2023

Prior Publication Data

Document Identifier **Publication Date**

US 20230314678 A1 Oct. 05, 2023

Foreign Application Priority Data

CN 201810921532.7

Aug. 14, 2018

Related U.S. Application Data

division parent-doc US 16508936 20190711 US 11714219 child-doc US 18331075

Publication Classification

Int. Cl.: **G01N21/35** (20140101); **G01N29/42** (20060101); **G02B1/04** (20060101); **G02B1/115** (20150101); **G02B5/20** (20060101); **G02B5/28** (20060101); **G02B13/14** (20060101)

U.S. Cl.:

CPC **G02B5/281** (20130101); **G01N21/35** (20130101); **G01N29/42** (20130101); **G02B1/115** (20130101); **G02B5/208** (20130101); **G02B5/288** (20130101); **G02B13/14** (20130101);

Field of Classification Search

CPC: G01N (21/35); G01N (21/359); G02B (1/04); G02B (1/115); G02B (5/208); G02B (5/281); G02B (5/285); G02B (5/288); G02B (13/14)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2852980	12/1957	Hubert	N/A	N/A
2920002	12/1959	Max	N/A	N/A
3514174	12/1969	Gans et al.	N/A	N/A
3528726	12/1969	Austin	N/A	N/A
3620626	12/1970	Daly et al.	N/A	N/A
3781111	12/1972	Fletcher et al.	N/A	N/A
3976875	12/1975	Engstrom et al.	N/A	N/A
3996461	12/1975	Sulzbach et al.	N/A	N/A
4158133	12/1978	Spaeth et al.	N/A	N/A
4835381	12/1988	Sorensen	N/A	N/A
4846541	12/1988	Miura et al.	N/A	N/A
4854670	12/1988	Mellor	N/A	N/A
5183700	12/1992	Austin	N/A	N/A
5242740	12/1992	Rostaing et al.	N/A	N/A
5258618	12/1992	Noble	N/A	N/A
5372874	12/1993	Dickey et al.	N/A	N/A
5398133	12/1994	Tsai et al.	N/A	N/A
5605609	12/1996	Ando et al.	N/A	N/A
6104530	12/1999	Okamura et al.	N/A	N/A
6115180	12/1999	Hirai et al.	N/A	N/A
6249378	12/2000	Shimamura et al.	N/A	N/A
6323942	12/2000	Bamji	N/A	N/A
6572975	12/2002	Dalakos	N/A	N/A
6809859	12/2003	Erdogan et al.	N/A	N/A
6936551	12/2004	Moghadam et al.	N/A	N/A

7049004	12/2005	Domash et al.	N/A	N/A
7068430	12/2005	Clarke et al.	N/A	N/A
7133197	12/2005	Ockenfuss et al.	N/A	N/A
7194209	12/2006	Robbins et al.	N/A	N/A
7247835	12/2006	Chang	N/A	N/A
7340077	12/2007	Gokturk et al.	N/A	N/A
7405880	12/2007	Nikolov et al.	N/A	N/A
7859754	12/2009	Falicoff	N/A	N/A
7901870	12/2010	Wach	430/321	G02B 5/28
7903338	12/2010	Wach	N/A	N/A
7993700	12/2010	Zhou et al.	N/A	N/A
8080776	12/2010	Kurahashi et al.	N/A	N/A
8227883	12/2011	Kasano et al.	N/A	N/A
8304727	12/2011	Lee et al.	N/A	N/A
8461533	12/2012	Findlay	N/A	N/A
8481109	12/2012	Zambov et al.	N/A	N/A
8852844	12/2013	Ogihara et al.	N/A	N/A
8861088	12/2013	Ohnishi	N/A	N/A
8993072	12/2014	Xiao et al.	N/A	N/A
9077868	12/2014	Pilgrim	N/A	N/A
9098931	12/2014	Shpunt et al.	N/A	N/A
9322965	12/2015	Osawa et al.	N/A	N/A
9354369	12/2015	Hendrix et al.	N/A	N/A
9550864	12/2016	Bloomfield	N/A	N/A
9570490	12/2016	Kakiuchi et al.	N/A	N/A
9588269	12/2016	Hendrix et al.	N/A	N/A
10168459	12/2018	Ockenfuss	N/A	N/A
10222526	12/2018	Hendrix et al.	N/A	N/A
10962477	12/2020	Won et al.	N/A	N/A
11131794	12/2020	Hendrix et al.	N/A	N/A
11714219	12/2022	Mu	359/359	G01N 21/35
2002/0080493	12/2001	Tsai et al.	N/A	N/A
2002/0154387	12/2001	Mori et al.	N/A	N/A
2003/0087121	12/2002	Domash et al.	N/A	N/A
2004/0001182	12/2003	Dyner	N/A	N/A
2007/0024779	12/2006	Sharp	N/A	N/A
2007/0189583	12/2006	Shimada et al.	N/A	N/A
2008/0006762	12/2007	Fadell et al.	N/A	N/A
2008/0013178	12/2007	Terada	N/A	N/A
2008/0105298	12/2007	Lu et al.	N/A	N/A
2008/0223436	12/2007	Boer et al.	N/A	N/A
2009/0002830	12/2008	Okamoto	N/A	N/A
2009/0294634	12/2008	Kurahashi et al.	N/A	N/A
2010/0007717	12/2009	Spektor et al.	N/A	N/A
2010/0020078	12/2009	Shpunt	N/A	N/A
2010/0118123	12/2009	Freedman et al.	N/A	N/A
2010/0284088	12/2009	Zambov et al.	N/A	N/A
2011/0232745	12/2010	Alves et al.	N/A	N/A
2011/0301500	12/2010	Maguire et al.	N/A	N/A
2011/0310472	12/2010	Hirai et al.	N/A	N/A

2012/0087645	12/2011	Wu et al.	N/A	N/A
2012/0099188	12/2011	Akozbebek et al.	N/A	N/A
2012/0145901	12/2011	Kakiuchi et al.	N/A	N/A
2012/0182392	12/2011	Kearns et al.	N/A	N/A
2012/0224061	12/2011	Pilgrim	N/A	N/A
2012/0268809	12/2011	Guo et al.	N/A	N/A
2012/0326191	12/2011	Fu	N/A	N/A
2013/0050811	12/2012	Lin et al.	N/A	N/A
2014/0014838	12/2013	Hendrix et al.	N/A	N/A
2015/0346403	12/2014	Jidai et al.	N/A	N/A
2016/0238759	12/2015	Sprague	N/A	C23C 14/06
2016/0266289	12/2015	Hendrix et al.	N/A	N/A
2020/0408977	12/2019	Eisenhammer	N/A	C23C 14/35

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
101421641	12/2008	CN	N/A
201378210	12/2009	CN	N/A
1892676	12/2009	CN	N/A
105452911	12/2016	CN	N/A
107209305	12/2016	CN	N/A
107710034	12/2017	CN	N/A
107841712	12/2017	CN	N/A
108303759	12/2017	CN	N/A
1816677	12/2006	EP	N/A
1879058	12/2007	EP	N/A
2016164670	12/2015	JP	N/A
20110086552	12/2010	KR	N/A
20170106448	12/2016	KR	N/A
20180008898	12/2017	KR	N/A
200513812	12/2004	TW	N/A
201743439	12/2016	TW	N/A
2011027903	12/2010	WO	N/A
2014088063	12/2013	WO	N/A
2014168190	12/2013	WO	N/A

OTHER PUBLICATIONS

Amorphous silicon and amorphous silicon nitride films prepared by a plasma-enhanced chemical vapor deposition process as optical coating materials Applied Optics vol. 32 No. 28 R.Y. Tsai (Oct. 1993). cited by applicant

Antireflective Coating Using Aluminum Hydroxide formed by Hydrothermal Treatment of Sputtered Aluminum Films. cited by applicant

A-Si:H/SiO₂ multilayer films fabricated by radio-frequency magnetron sputtering for optical filters Applied Optics vol. 43 No. 17 H. Yoda (2004). cited by applicant

Characterization of hydrogenated amorphous silicon thin films prepared by magnetron sputtering J. of Non-Crystalline Solids 352 (2006) 18-23 M. Hossain. cited by applicant

China Patent Office, Office Action, Apr. 27, 2021. cited by applicant

Chinese Patent Office Notice of Allowance; Application No. 201810921532.7, dated Jul. 28, 2021, 4 pages. cited by applicant

Coating design contest: antireflection coating for lenses to be used with normal and infrared

photographic film Proc. SPIE 1782 Thin Films for Optical Systems pp. 552-601 (Mar. 4, 1993). cited by applicant

Defendant Platinum Optics Technology Inc.'s Invalidity Contentions from Case No. 5:20-cv-05501, Dated Jan. 15, 2021. cited by applicant

Deposition parameters and film properties of hydrogenated amorphous silicon prepared by high rate dc planar magnetron reactive sputtering J. Appl. Phys. 55 4232 (1984) N. Savvides. cited by applicant

Development and Implementation of a Hydrogenated a-Si Reactive Sputter Deposition Process Society of Vacuum Coaters K. Gibbons (2007). cited by applicant

Effect of hydrogen dilution of silane on optoelectronic properties in glow-discharged hydrogenated silicon films J. Appl. Phys. 58 3661 (1985) S. Shirafuji. cited by applicant

Effective Refractive Index as a Criterion of Performance of Interference Filters J. of the Optical Society of Am. vol. 58 No. 12 P.H. Lissberger (Dec. 1968). cited by applicant

Effects of the Variation of Angle of Incidence and Temperature on Infrared Filter Characteristics (Baker and Yen). cited by applicant

Evolution of microstructures in hydrogenated silicon films prepared by diluted-hydrogen and hydrogen-atom-treatment methods J. Appl. Phys. 73 (10) (May 15, 1993) K.C. Hsu. cited by applicant

Handbook of Optics I: Part 11 Chapter 42: Optical Properties of Films and Coatings J.A. Dobrowolski (1995). cited by applicant

How Microsoft's PrimeSense-Based Kinect Really Works (William Wong. cited by applicant

How Motion Detection Works in Xbox Kinect (Wired) (Tim Carmody). cited by applicant

Hydrogenated Amorphous Silicon Alloy Deposition Processes. cited by applicant

Hydrophobic and Optical Properties of Silica Antireflective Coating Prepared via Sol-Gel Method (Zhang). cited by applicant

Influence of Sputtering Conditions on H Content and Si—H Bonding IN a-Si:H Alloys (P.M. Martin and W.T. Pawlewicz). cited by applicant

Kinect Manual. cited by applicant

Kinect Unleashed: Getting Control over High Resolution Depth Maps (Manuel Martinez and Rainer Stiefelhagen). cited by applicant

Kinetics of decomposition of amorphous hydrogenated silicon films J. Appl. Phys. 50 5238 (1979) J. A. McMillan. cited by applicant

Microsoft Kinect: Features and Implementation (Francesco Castaldo). cited by applicant

Microstructure and properties of rf-sputtered amorphous hydrogenated silicon films JAppl. Phys. 52 5329 (1981) R. C. Ross et al. cited by applicant

Notice of Allowance for Korean Patent Application No. 10-2019-0054163 dated Nov. 18, 2020; 2 pgs. cited by applicant

Office Action for Korean Patent Application No. 10-2019-0054163 dated May 26, 2020; 7 pgs. cited by applicant

Optical and structural properties of hydrogenated silicon films prepared by rf-magnetron sputtering at low growth temperatures: Study as a function of argon gas dilution J. on Non-Crystalline Solids 358 (2012) 854-859 Y. Bouizem. cited by applicant

Optical Filter on the Window on 0~25 Degree Incidence Angle 980nm Semiconductor Detector 2010 Academic Symposium on Optoelectronics and Microelectronics Technology and 10th Chinese-Russian Symposium on Laser Physics and Laser Technology Optoelectronics Technology (ASOT) Harbin 2010 L. Peng (2010). cited by applicant

Optical properties of a-Si and a-Si:H prepared by DC magnetron techniques J. Phys C: Solid State Phys. 16 (1983) 4933-4944 (1983) D.R. McKenzie. cited by applicant

Optical properties of hydrogenated amorphous silicon J. Appl. Phys. 59 611 (1986) F. Demichelis et al. cited by applicant

Optical Properties of Sputtered Si: H (P.M. Martin W.T. Pawlewicz I.B. Mann). cited by applicant

Optical Thin Films: User Handbook. cited by applicant

Ow You Become the Controller (Ron Forbes). cited by applicant

Patent Trial and Appeal Board, IPR2021-00424 Ipr Petition, Dated Jan. 19, 2021. cited by applicant

Patent Trial and Appeal Board, IPR2021-00432 Ipr Petition, Dated Feb. 4, 2021. cited by applicant

Patent Trial and Appeal Board, IPR2021-00631 Ipr Petition, Dated Mar. 29, 2021. cited by applicant

Patent Trial and Appeal Board, IPR2022-01489 Ipr Petition, Dated Sep. 6, 2022. cited by applicant

Plasma Deposition of Optical Films and Coatings: A Review (L. Martinu and D. Poitras. cited by applicant

Practical Design of Optical Thin Films 2nd Ed. R.R. Willey. cited by applicant

PrimeSense Reference Design. cited by applicant

Process investigation of a-Si:H thin films prepared by DC magnetron sputtering Proc. SPIE 6825 Lasers in Material Processing and Manufacturing III 682514 (Jan. 2008) L. Chunling. cited by applicant

Recent Developments in Reactively Sputtered Optical Thin Films (W.T. Pawlewicz). cited by applicant

Reduced Angle-Shift Infrared Bandpass Filter Coatings Proc. of SPIE vol. 6545 Window and Dome Technologies and Materials X 654501 B.M. Lairson (May 2007). cited by applicant

Resolving Power of Multilayer Filters in Nonparallel Light (C.R. Pidgeon and S.D. Smith). cited by applicant

Rugate filters fabricated by a radio frequency magnetron sputtering system by use of an optical in situ monitoring technique Applied Optics vol. 45 No. 1 H. Yoda (Jan. 2006). cited by applicant

Silicon Nitride (Si₃N₄) (Noncrystalline) Handbook of Optical Constants of Solids pp. 771-774 (1985) H.R. Philipp. cited by applicant

Silicon Nitride ARC Thin Films by New Plasma Enhanced Chemical Vapor Deposition Source Technology (M. George H. Chandra P. Morse J. Morris and J. Madocks. cited by applicant

Sputtered hydrogenated amorphous silicon thin films for distributed Bragg reflectors and long wavelength vertical cavity surface emitting lasers and applications Thin Solid Films 519 (2011) 6178-6182 A. Shuaib. cited by applicant

Sputtered Si:H alloys for edge filters: application to thermophotovoltaics Applied Optics vol. 41 No. 31 (Nov.1 2002) P. M. Martin. cited by applicant

Stable ultranarrow bandpass filters Proc. SPIE 2262 Optical Thin Films IV: New Developments (Sep. 7 1994) M. Scobey. cited by applicant

Structure and optical properties of the hydrogen diluted a-Si:H thin films prepared by PECVD with different composition temperatures The Eighth International Conference on Advanced Semiconductor Devices and Microsystems Smolenice 2010 pp. 329-332 films prepared by PECVD with different composition temperatures films prepared by PECVD with different composition temperatures M. Netrvalova (2010). cited by applicant

Taiwan Patent Office, Office Action, Jul. 19, 2019. cited by applicant

The Reflective Properties of Broadband Optical Multilayers Acta Physica Sinica vol. 6 No. 5 (May 1997) Z. Dao-Zhong. cited by applicant

Thin-Film Optical Filters Second Ed. (McGraw-Hill 1989) H. A. Macleod. cited by applicant

Tunable and Switchable Multiple-Cavity Thin Film Filters J. Lightwave Technol. Vol. 22 No. 1 (2004) L. Domash. cited by applicant

Xbox 360 Kinect Teardown—The Kinect is a Peripheral Containing Suite of Sensors for Microsoft's Xbox 360 that provides a “Controller-Free Gaming and Entertainment Experience.” (Kyle Wiens). cited by applicant

Background/Summary

CROSS REFERENCE TO RELATED APPLICATION (1) This application is a divisional application of U.S. patent application Ser. No. 16/508,936, filed on Jul. 11, 2019, which claims the priority benefit of Chinese Patent Application Serial Number 201810921532.7, filed on Aug. 14, 2018, the full disclosure of which is incorporated herein by reference.

BACKGROUND

Technical Field

(1) The present disclosure relates to the technical field of optical filtering, and more particularly to an infrared band pass filter.

Related Art

(2) The existing infrared band pass filter comprises an optical substrate having a multilayer film formed on one surface of the optical substrate, and a multilayer anti-refraction layer formed on the other surface thereof. The multilayer film is formed by alternately depositing a plurality of high refractive index layers and a plurality of low refractive index layers. The material of the high refraction index layer is selected from the group consisting of TiO_2 , Ta_2O_5 , ZrO_2 , Nb_2O_5 and TiO_2 and the material of the low refraction index layer is selected from one of the MgF_2 and SiO_2 .

(3) The infrared band pass filter has a pass band in the wavelength range between 800 nm and 1100 nm. When the incident angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted between 31 nm and 34 nm. The center wavelength of the pass band is greatly shifted due to the angle changed, and when the infrared band pass filter is applied to the three-dimensional (3D) imaging system, the problem of unrecognizable or identification failure occurs when the light is received at a large angle.

SUMMARY

(4) The present disclosure provides an infrared band pass filter, comprising: a first multilayer film, wherein the first multilayer film comprises: a plurality of Si:NH layers, wherein the refraction index of each Si:NH layer is larger than 3.5 in the wavelength range between about 800 nm and 1100 nm, and the extinction coefficient of the each Si:NH layer is smaller than 0.0002; and plurality of low refraction index layers a plurality of low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein the refraction index of each low refraction index layer is smaller than 3 in the wavelength range between 800 nm and 1100 nm; wherein an difference value between the refraction index of the each Si:NH layer and the low refraction index layer is larger than 0.5.

(5) According to one embodiment of the present disclosure, the infrared band pass filter further comprises a substrate; the first multilayer film is formed on one surface of the substrate.

(6) According to one embodiment of the present disclosure, the infrared band pass filter further comprises a second multilayer film which is formed on the other surface of the substrate, being opposite to the first multilayer film.

(7) According to one embodiment of the present disclosure, the second multilayer film comprises: a plurality of Si:NH layers, wherein the refraction index of each Si:NH layer is larger than 3.5 in the wavelength range between about 800 nm and 1100 nm, and the extinction coefficient of the each Si:NH layer is smaller than 0.0002; and plurality of low refraction index layers a plurality of low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein the

refraction index of each low refraction index layer is smaller than 3 in the wavelength range between 800 nm and 1100 nm; wherein an difference value between the refraction index of the each Si:NH layer and the low refraction index layer is larger than 0.5.

(8) According to one embodiment of the present disclosure, the infrared band pass filter has a pass band partially overlapping with the wavelength range between 800 nm and 1100 nm, and the center wavelength of pass band is within the wavelength range between 800 nm and 1100 nm, and having a blocking level greater than OD5 in the wavelength range between 400 nm and 1100 nm.

(9) According to one embodiment of the present disclosure, the infrared band pass filter has a pass band partially overlapping with the wavelength range between 800 nm and 1100 nm, and the center wavelength of the pass band is in the wavelength range between 800 nm and 1100 nm.

(10) According to one embodiment of the present disclosure, when the incident angle is changed from 0 degrees to 30 degrees, and the center wavelength of the pass band is shifted less than 12 nm.

(11) According to one embodiment of the present disclosure, the sum of the number of layers of the Si:NH layer and the number of layers of the low refraction index layer is less than 39 layers.

(12) According to one embodiment of the present disclosure, the total thickness of the plurality of Si:NH layers and the plurality of low refraction index layers is less than 4.5 μm .

(13) According to one embodiment of the present disclosure, the hardness of infrared band pass filter is greater than Mohs hardness 7.

(14) According to one embodiment of the present disclosure, the material of the low refraction index layer is selected from the group consisting of SiO_2 , Al_2O_3 , TiO_2 , Nb_2O_5 , Ta_2O_5 , SiOH and SiNOH .

(15) According to one embodiment of the present disclosure, the material of the low refraction index layer is SiO_2 , the refraction index of the low refraction index layer is between 1.4 and 1.5 in a wavelength range between 800 nm and 1100 nm.

(16) According to the embodiment of the present disclosure, when the incident angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted less than 11.8 nm.

(17) According to one embodiment of the present disclosure, the material of the low refraction index layer is SiNOH , the refraction index of the low refraction index layer is between 1.5 and 2 in a wavelength range between 800 nm and 1100 nm.

(18) According to one embodiment of the present disclosure, when the incident angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted less than 11.1 nm.

(19) According to one embodiment of the present disclosure, the hardness of infrared band pass filter is greater than Mohs hardness 9.

(20) According to one embodiment of the present disclosure, the extinction coefficient of the Si:NH layer is less than 0.00012 in the wavelength range between 800 nm and 1100 nm.

(21) According to one embodiment of the present disclosure, the transmissivity of pass band is greater than 90% in the wavelength between 800 nm and 1100 nm.

(22) Compared with the prior art, the present disclosure can obtain the following technical effects:

(23) The present disclosure provides an infrared band pass filter. The infrared band pass filter of the present disclosure is formed by alternatively stacking a Si:NH layer and a low refraction index layer, which has a pass band in a wavelength range between 800 nm and 1100 nm. When the incident angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted less than 12 nm, and the infrared band pass filter of the present disclosure can be applied to the 3D imaging system to improve the 3D image analysis capability.

(24) It should be understood, however, that this summary may not contain all aspects and embodiments of the present disclosure, that this summary is not meant to be limiting or restrictive in any manner, and that the disclosure as disclosed herein will be understood by one of ordinary skill in the art to encompass obvious improvements and modifications thereto.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The features of the exemplary embodiments believed to be novel and the elements and/or the steps characteristic of the exemplary embodiments are set forth with particularity in the appended claims. The Figures are for illustration purposes only and are not drawn to scale. The exemplary embodiments, both as to organization and method of operation, may best be understood by reference to the detailed description which follows taken in conjunction with the accompanying drawings in which:

(2) FIG. 1 shows the schematic diagram of an infrared band pass filter according to a first embodiment of present disclosure;

(3) FIG. 2 shows a curve graph of the transmission spectrum of the Si:NH layer according to the first embodiment of the present disclosure;

(4) FIG. 3 shows curve graph of the transmission spectrum of incident angle from 0 degrees to 30 degrees of the infrared band pass filter;

(5) FIG. 4 shows the infrared band pass filter according to a second embodiment;

(6) FIG. 5 shows the curve graph of the transmission spectrum of incident angle from 0 degrees to 30 degrees of the first multilayer film according to the second embodiment;

(7) FIG. 6 shows the curve graph of the transmission spectrum of incident angle from 0 degrees to 30 degrees of the second multilayer film according to the second embodiment; and

(8) FIG. 7 shows the curve graph of the transmission spectrum of incident angle from 0 degrees to 30 degrees of the infrared band pass filter according to the second embodiment.

DETAILED DESCRIPTION OF THE EMBODIMENTS

(9) The present disclosure will now be described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments of the disclosure are shown. This present disclosure may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this present disclosure will be thorough and complete, and will fully convey the scope of the present disclosure to those skilled in the art.

(10) Certain terms are used throughout the description and following claims to refer to particular components. As one skilled in the art will appreciate, manufacturers may refer to a component by different names. This document does not intend to distinguish between components that differ in name but function. In the following description and in the claims, the terms “include/including” and “comprise/comprising” are used in an open-ended fashion, and thus should be interpreted as “including but not limited to”. “Substantial/substantially” means, within an acceptable error range, the person skilled in the art may solve the technical problem in a certain error range to achieve the basic technical effect. The following description is of the best-contemplated mode of carrying out the disclosure. This description is made for the purpose of illustration of the general principles of the disclosure and should not be taken in a limiting sense. The scope of the disclosure is best determined by reference to the appended claims.

(11) Moreover, the terms “include”, “contain”, and any variation thereof are intended to cover a non-exclusive inclusion. Therefore, a process, method, object, or device that includes a series of elements not only includes these elements, but also includes other elements not specified expressly, or may include inherent elements of the process, method, object, or device. If no more limitations are made, an element limited by “include a/an . . .” does not exclude other same elements existing in the process, the method, the article, or the device which includes the element.

(12) In the following embodiment, the same reference numerals is used to refer to the same or similar elements throughout the disclosure.

(13) FIG. 1 shows the schematic diagram of an infrared band pass filter according to a first

embodiment of present disclosure. As shown in FIG. 1, the embodiment provides an infrared band pass filter **1** adapted for a 3D imaging system. The infrared band pass filter **1** comprises a first multilayer film **11**. The first multilayer film **11** comprises a plurality of Si:NH layers **111** and a plurality of low refraction index layers **112**, and the plurality of low refraction index layers **112** are stacking with the plurality of Si:NH layers alternatively. The refraction index of each Si:NH layer **111** is larger than 3.5 in the wavelength range between 800 nm and 1100 nm, and the extinction coefficient of the each Si:NH layer is smaller than 0.0002. In another embodiment, the extinction coefficient of the each Si:NH layer less than 0.00012. The refraction index of each low refraction index layer **112** is smaller than 3 in the wavelength range between 800 nm and 1100 nm; wherein an difference value between the refraction index of the each Si:NH layer **111** and the low refraction index layer **112** is larger than 0.5.

(14) In the embodiment, the sum of the number of Si:NH layers **111** and the number of low refraction index layer **112** is smaller than 39 layers. The total thickness of the plurality of Si:NH layers **111** and the plurality of low refraction index layers **112** is smaller than 4.5 μm . In the embodiment, the infrared band pass filter **1** has some band pass overlapping the wavelength range between 800 nm and 1100 nm. The center wavelength of the band pass is located in the wavelength range between 800 nm and 1100 nm.

(15) While the incidence angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted less than 12 nm. Transmissivity of the band pass is larger 90% in the wavelength range between 800 nm and 1100 nm. In the embodiment, the hardness of the infrared band pass filter is larger than Mohs' hardness 7. In the embodiment, the center wavelength of the big angle of the infrared band pass filter **1** being smaller can solve the 3D imaging analyze problem effectively, while the thickness of the infrared band pass filter **1** of the present embodiment is slimmer than the infrared band pass filter of the prior technology so as to decrease the warping phenomenon of the infrared band pass filter **1**.

(16) In the embodiment, manufacture method of the infrared band pass filter **1** is to form the Si:NH layer **111** and the low refraction index layer **112** by the sputter deposition. The process of the sputter deposition is that the mid frequency sputter power source output 50 KHz voltage through the inside electrical network, respectively applied on a pair of silicon target on the sputtering machine. Argon is inputted into the silicon target via the air duct so as to generate light and discharge and generate the steady plasma.

(17) Due to the reaction chamber of the sputtering machine has the quadrature field being vertical to the electrical filed, the movement direction of the electron is changed and limited in the certain space so as to increase the collision probability with the argon and ionization effect of electron.

(18) The argon ion elected from ionization effect crash the silicon target quickly in the electrical field, and the mass silicon atom is sputtered out, while inductively coupled plasma (ICP) is mixed with ammonia to generate the Si:NH layer **111** which has the refraction index larger than 3.5 in the wavelength range between 800 nm and 1100 nm. The low refraction index layer **112** is selected from the group consisting of SiO₂, SiOH or SiNOH, and the ICP is mixed with oxygen/ammonia to generate the low refraction index layer which the refraction index is smaller than 3 in the wavelength range between 800 nm and 1000 nm. If the low refraction index layer **112** is Al₂O₃, TiO₂ or Nb₂O₅ or Ta₂O₅, the silicon target of the sputtering machine is replaced with an aluminum target, a titanium target, a tantalum target or a tantalum target, and formed by the above method.

(19) TABLE-US-00001

TABLE 1	At 940 nm	At 940 nm	TG4 gas	ICP gas	n	k	Material
Argon	Argon	oxygen	Ammonia	(Opt)	(Opt)	SiNOH	60 500 5 30 3.42022 8.35E-05
SiNOH	60 500 10 30	3.267666	6.24E-05	SiNOH	60 500 30 30	2.781278	3.23E-05
SiNOH	60 500 70 30	2.176382	2.27E-04	SiNOH	60 500 76 30	2.125067	2.60E-04
SiNOH	60 500 80 30	2.037629	1.85E-04	SiNOH	60 500 88 30	1.986488	1.94E-04
SiNOH	60 500 95 30	1.908388	1.42E-04	SiNOH	60 500 104 30	1.846262	1.69E-04
SiNOH	60 500 125 30	1.576734	1.26E-05				

(20) As shown in Table 1, the refraction index of the low refraction layer **112** of the embodiment will be changed along with the change of the oxygen flow via the spurring process in the wavelength 940 nm. When the oxygen flow is becoming bigger, then the refraction index of the low refraction index layer **112** in the wavelength 940 nm is becoming lower. When the low refraction index layer **112** is SiNOH, the refraction index of the low refraction index layer **112** is between 1.5 and 2 in the wavelength range between 800 nm and 1100 nm. When the low refraction index layer **112** is SiO.sub.2, the refraction index of the low refraction index layer **112** is between 1.4 and 1.5 in the wavelength range between 800 nm and 1100 nm.

(21) FIG. 2 shows a curve graph of the transmission spectrum of the Si:NH layer according to the first embodiment of the present disclosure. As shown in FIG. 2, the curve **21** is the transmission spectrum of the Si:NH layer and the curve **22** is the transmission spectrum of the Ti.sub.3O.sub.5 layer. The absorption effect of the Si:NH layer **111** is better than the Ti.sub.3O.sub.5 layer used by the infrared band pass filter in the wavelength range between 350 nm and 700 nm. The infrared band pass filter **1** having Si:NH layer is applied in the 3D image system so as to increase the image analyze function of the 3D image system.

(22) The material of the low refraction index layer **112** is selected from the group consisting of SiO.sub.2, Al.sub.2O.sub.3, TiO.sub.2, Nb.sub.2O.sub.5, Ta.sub.2O.sub.5, SiOH and SiNOH. The material of the low refraction index layer **112** is SiO.sub.2, the refraction index of the low refraction index layer **112** is between 1.4 and 1.5 in the wavelength range between 800 nm and 1100 nm. The sum of the number of Si:NH layers **111** and the number of low refraction index layer **112** is 39 layers. The sum of thickness of the plurality of Si:NH layers **111** and the plurality of low refraction index layers **112** is 4.4 μm . Table 2 shows the thickness list of each Si:NH layer **111** and each low refraction index layer **112**.

(23) TABLE-US-00002

TABLE 2	Number	thickness	Number	thickness	Number	Thickness of
layers material	(nm)	of layers material	(nm)	of layers material	(nm)	1 SiO.sub.2
21.84	27	SiO.sub.2	121.07	2	Si:NH	253.51
118.19	16	Si:NH	99.93	29	SiO.sub.2	300.84
SiO.sub.2	306.22	18	Si:NH	41.78	31	SiO.sub.2
49.42	7	SiO.sub.2	78.43	20	Si:NH	61.93
34	Si:NH	15.21	9	SiO.sub.2	70.53	22
SiO.sub.2	106.84	36	Si:NH	4.87	11	SiO.sub.2
Si:NH	233.19	25	SiO.sub.2	128.68	38	Si:NH
SiO.sub.2	15.54					

(24) FIG. 3 shows curve graph of the transmission spectrum of incident angle from 0 degrees to 30 degrees of the infrared band pass filter. As shown in FIG. 3, it shows the transmission spectrum curve **31** in the incident angle of 0 degrees and the transmission spectrum curve **32** in the incident angle of 30 degrees. The center wavelength of the band pass is 946 nm in the incident angle of 0 degrees in the embodiment. The center wavelength of the band pass is 934.2 nm in the incident angle of 30 degrees in the embodiment. Therefore, when the incident angle of the infrared band pass filter is changed from 0 degrees to 30 degrees, the offset amplitude of the center wavelength of the band pass is smaller than 11.8 nm. The transmissivity of the band pass is larger than 90% in the wavelength range between 800 nm and 1100 nm.

(25) FIG. 4 shows the infrared band pass filter according to a second embodiment. As shown in FIG. 4, the infrared band pass filter **1** comprises a first multilayer film **11a**, a second multilayer film **11b** and an optical substrate **12**. The first multilayer film **11a** and the second multilayer film **11b** are respectively arranged the two opposite surfaces **121** of the optical substrate **12**. Specifically, the first multilayer film **11a** and the second multilayer film **11b** respectively has a structure of the plurality of Si:NH layers **111** alternatively stacking with the plurality of low refraction index layers **112**. The manufacture methods of the Si:NH layer **111** and the low refraction index layer **112** are

described above. In the embodiment, the thickness of the infrared band pass filter is slimmer than the infrared band pass filter of the prior technology, and while the infrared band pass filter **1** of the embodiment has two multilayer films, the two multilayer films will be maintained balance via film stress so as to decrease the warp phoneme happen of the infrared band pass filter.

(26) In the infrared band pass filter **1** of the embodiment, the material of the low refraction index layer **112** of the first multilayer film **11a** is SiNOH. The sum of the number of the Si:NH layer **111** and the number of the low refraction index layer **112** is 39 layers. The total thickness of the plurality of Si:NH layer **111** and the plurality of low refraction index layer **112** is 4.3 um. Table 3 shows the thickness list of the each Si:NH layer **111** and each low refraction index layer **112**.

(27) TABLE-US-00003 TABLE 3 Number Thickness of layers Material (nm)

1	SiNOH	297.2
2	Si:NH	15.1
3	SiNOH	38.88
4	Si:NH	115.6
5	SiNOH	211.44
6	Si:NH	280.91
7	SiNOH	62.06
8	Si:NH	79.67
9	SiNOH	50.49
10	Si:NH	70.88
11	SiNOH	81.85
12	Si:NH	306.07
13	SiNOH	19.97
14	Si:NH	104
15	SiNOH	103.41
16	Si:NH	124.59
17	SiNOH	38.43
18	Si:NH	99.3
19	SiNOH	55.11
20	Si:NH	295.27
21	SiNOH	28.61
22	Si:NH	108.38
23	SiNOH	74.2
24	Si:NH	105.09
25	SiNOH	114.44
26	Si:NH	127.7
27	SiNOH	69.68
28	Si:NH	121.36
29	SiNOH	6.85
30	Si:NH	288.78
31	SiNOH	44.21
32	Si:NH	102.59
33	SiNOH	14.23
34	Si:NH	112.35
35	SiNOH	83.11
36	Si:NH	299.68
37	SiNOH	14.19
38	Si:NH	89.14
39	SiNOH	80.45

(28) Please refer to FIG. 5, which shows the curve graph of the transmission spectrum of incident angle from 0 degrees to 30 degrees of the first multilayer film according to the second embodiment of the present disclosure; as shown in FIG. 5, which shows the transmission spectrum curve **41** at the incident angle 0 degrees and the transmission spectrum curve **42** at the incident angle 30 degrees. In the present embodiment, the center wavelength of band pass is in 939.9 nm at an incident angle of 0 degrees and the center wavelength is in 932.8 nm at an incident angle of 30 degrees. Therefore, when the infrared band pass filter of the present embodiment is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted less than 11.1 nm. The transmission of the pass band in the wavelength range between 800 nm and 1100 nm is more than 90%.

(29) However, the material of the low refraction index layer **112** of the second multilayer film **11b** of the present embodiment also uses SiNOH, and the total number of layers of the Si:NH layer **111** and the low refraction index layer **112** is 32 layers. The total thickness of the plurality of Si:NH layers **111** and a plurality of low refraction index layers **112** of the second multilayer film **11b** is 2.7 um. The Table 3 below lists the thicknesses of each Si:NH layer **111** and the low refraction index layer **112**.

(30) TABLE-US-00004 TABLE 3 Number Thickness of layers Material (nm)

1	SINOH	20.84
2	SINH	85.77
3	SINOH	121.13
4	SINH	72.85
5	SINOH	128.99
6	SINH	138
7	SINOH	108.69
8	SINH	49.76
9	SINOH	150.76
10	SINH	110.88
11	SINOH	47.85
12	SINH	121.71
13	SINOH	145.74
14	SINH	127.98
15	SINOH	63.26
16	SINH	122.03
17	SINOH	31.33
18	SINH	91.1
19	SINOH	46.32
20	SINH	101.34
21	SINOH	53.27
22	SINH	99.56
23	SINOH	57.74
24	SINH	71.18
25	SINOH	45.12
26	SINH	96.14
27	SINOH	52.1
28	SINH	91.74
29	SINOH	56.67
30	SINH	73.42
31	SINOH	19.03
32	SINH	72.95

(31) Referring to FIG. 6 and FIG. 7 again, it shows the curve graph of the transmission spectrum of the second multilayer film of the second embodiment of the present disclosure at an incident angle of 0 degrees and 30 degrees, and the curve graph of the transmission spectrum of the infrared band pass filter of the second embodiment of the present disclosure at an incident angle of 0 degrees and 30 degrees. As shown in FIG. 6, the transmission spectrum curve **51** at the incident angle 0 degrees and the transmission spectrum curve **52** at the incidence angle 30 degrees. The second multilayer film **11b** of the present embodiment is used to increases the transmissivity of the infrared band pass filter. As can be seen from FIG. 6, the transmissivity of the pass band of the infrared band pass filter in the wavelength range between 800 nm and 1100 nm is greater than 90%, meanwhile, the outside of the pass band of the infrared band pass filter has a blocking level which is larger than

OD5 in the wavelength range between 400 nm and 1100 nm. FIG. 7 shows the transmission spectrum curve **61** at an incident angle 0 degrees and the transmission spectrum curve **62** at an incident angle 30 degrees. The infrared band pass filter of the present embodiment, at an incident angle 0 degrees, has the center wavelength of the pass band being at 943.9 nm. The infrared band pass filter of this embodiment, at an incident angle 30 degrees, the center wavelength of pass band being at 932.8 nm. Therefore, when the infrared band pass filter of the present embodiment is changed from 0 degrees to 30 degrees, the shift wavelength of the center wavelength of the pass band is less than 11.1 nm.

(32) The Mohs hardness of the infrared band pass filter of the embodiment can achieve to 9 and 9.5. The Vickers hardness is about 2200, and the micro-hardness is 32630 MPa, thus demonstrating that the infrared band pass filter of the embodiment has good chemical resistance, and having a good chemical corrosion resistance under inorganic acid, less than 30% caustic soda solution or organic acid, also being a high performance electrical insulation material. The material of the low refraction index layer **112** of the first multilayer film **11a** and the second multilayer film **11b** of the present embodiment can also be made of other materials such as SiO.sub.2 custom character Al.sub.2O.sub.3 custom character TiO.sub.2 custom character Nb.sub.2O.sub.5 custom character Ta.sub.2O.sub.5 or SiOH. The stacked of the Si:NH layer **111** and the low refraction index layer **112** of the first multilayer film **11a** and the stacked of the Si:NH layer **111** and the low refraction index layer **112** of the second multilayer film **11b** of the present embodiment are mutually change.

(33) In summary, in one or more embodiments of the present disclosure, the present disclosure provides an infrared band pass filter, which having at least one multilayer film. The multilayer film is formed by the Si:NH layer and the low refraction index layer alternatively stacked, which having a pass band in a wavelength range between 800 nm and 1100 nm. When the incident angle is changed from 0 degrees to 30 degrees, the center wavelength of the pass band is shifted by less than 12 nm. The shift of the large-angle center wavelength of the infrared band pass filter of the present disclosure is small, and the infrared band pass filter of the present disclosure can improve the three-dimensional image resolution capability when applied to a three-dimensional imaging system.

(34) It is to be understood that the term “comprises”, “comprising”, or any other variants thereof, is intended to encompass a non-exclusive inclusion, such that a process, method, article, or device of a series of elements not only includes those elements but also includes other elements that are not explicitly listed, or elements that are inherent to such a process, method, article, or device. An element defined by the phrase “comprising a . . .” does not exclude the presence of the same element in the process, method, article, or device that comprises the element.

(35) Although the present disclosure has been explained in relation to its preferred embodiment, it does not intend to limit the present disclosure. It will be apparent to those skilled in the art having regard to this present disclosure that other modifications of the exemplary embodiments beyond those embodiments specifically described here may be made without departing from the spirit of the disclosure. Accordingly, such modifications are considered within the scope of the disclosure as limited solely by the appended claims.

Claims

1. An infrared band pass filter, comprising: a first multilayer film, wherein the multilayer film comprises: a plurality of Si:NH layers, wherein a refraction index of each Si:NH layer is larger than 3.5 in a wavelength range between 800 nm and 1100 nm; and a plurality of first low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein a refraction index of each first low refraction index layer is smaller than 3 in the wavelength range between 800 nm and 1100 nm; a substrate, wherein the substrate is formed on the first multilayer film; and a second

multilayer film, formed on the other surface of the substrate, opposite to the first multilayer film, and wherein the second multilayer film comprises: a plurality of Si:NH layers, wherein a refraction index of each Si:NH layer is greater than 3.5 in the wavelength range between 800 nm and 1100 nm; and a plurality of second low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein a refraction index of each second low refraction index layer is less than 3 in the wavelength range between 800 nm and 1100 nm; wherein the substrate directly contacts the Si:NH layer of the first multilayer film and the Si:NH layer of the second multilayer film.

2. The infrared band pass filter of claim 1, wherein a material of the first low refraction index layer is selected from Al₂O₃ and SiNOH, and a material of the second low refraction index layer is selected from Al₂O₃ and SiNOH.

3. The infrared band pass filter of claim 1, wherein a total thickness of the plurality of Si:NH layers in the first multilayer film is the same as a total thickness of the plurality of Si:NH layers in the second multilayer film, and a total thickness of the plurality of first low refraction index layers in the first multilayer film is the same as a total thickness of the plurality of second low refraction index layers in the second multilayer film.

4. The infrared band pass filter of claim 1, wherein a wavelength range in which a transmissivity of the first multilayer film is greater than 90% is smaller than a wavelength range in which a transmissivity of the second multilayer film is greater than 90%.

5. The infrared band pass filter of claim 1, wherein when an incident angle is changed from 0 degrees to 30 degrees, a center wavelength of a pass band of the infrared band pass filter is shifted less than 12 nm.

6. The infrared band pass filter of claim 1, wherein a layer farthest from the substrate in the first multilayer film is the first low refraction index layer, and a layer farthest from the substrate in the second multilayer film is the second low refraction index layer.

7. The infrared band pass filter of claim 6, wherein a material of the layer farthest from the substrate in the first multilayer film is SiNOH, and a material of the layer farthest from the substrate in the second multilayer film is SiNOH.

8. An infrared band pass filter, comprising: a first multilayer film, wherein the multilayer film comprises: a plurality of Si:NH layers, wherein a refraction index of each Si:NH layer is larger than 3.5 in a wavelength range between 800 nm and 1100 nm; and a plurality of first low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein a material of the first low refraction index layer is selected from the group consisting of SiO₂, Al₂O₃, TiO₂, Nb₂O₅, Ta₂O₅, SiOH and SiNOH; a substrate, wherein the substrate is formed on the first multilayer film; and a second multilayer film, formed on the other surface of the substrate, opposite to the first multilayer film, and wherein the second multilayer film comprises: a plurality of Si:NH layers, wherein a refraction index of each Si:NH layer is greater than 3.5 in the wavelength range 800 nm and 1100 nm; and a plurality of second low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein a material of the second low refraction index layer is selected from the group consisting of SiO₂, Al₂O₃, TiO₂, Nb₂O₅, Ta₂O₅, SiOH and SiNOH; wherein the substrate directly contacts the Si:NH layer of the first multilayer film and the Si:NH layer of the second multilayer film.

9. The infrared band pass filter of claim 8, wherein a total thickness of the plurality of Si:NH layers in the first multilayer film is the same as a total thickness of the plurality of Si:NH layers in the second multilayer film, and a total thickness of the plurality of first low refraction index layers in the first multilayer film is the same as a total thickness of the plurality of second low refraction index layers in the second multilayer film.

10. The infrared band pass filter of claim 8, wherein a layer farthest from the substrate in the first multilayer film is the first low refraction index layer, and a layer farthest from the substrate in the second multilayer film is the second low refraction index layer.

11. The infrared band pass filter of claim 8, wherein a hardness of the infrared band pass filter is greater than Mohs hardness 7.

12. The infrared band pass filter of claim 8, wherein when an incident angle is changed from 0 degrees to 30 degrees, a shift amount of a center wavelength of a pass band of the infrared band pass filter is from 11.1 nm to 12 nm.

13. The infrared band pass filter of claim 8, wherein when an incident angle is changed from 0 degrees to 30 degrees, a center wavelength of a pass band of the infrared band pass filter is shifted less than 12 nm.

14. The infrared band pass filter of claim 8, wherein a difference value between the refraction index of the Si:NH layer and the refraction index of the first low refraction index layer in the first multilayer film is larger than 0.5, and a difference value between the refraction index of the Si:NH layer and the refraction index of the second low refraction index layer in the second multilayer film is larger than 0.5.

15. An infrared band pass filter, comprising: a first multilayer film, wherein the multilayer film comprises: a plurality of Si:NH layers, wherein a refraction index of each Si:NH layer is larger than 3.5 in a wavelength range between 800 nm and 1100 nm; and a plurality of first low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein a refraction index of each first low refraction index layer is smaller than 3 in the wavelength range between 800 nm and 1100 nm; a substrate, wherein the substrate is formed on the first multilayer film; and a second multilayer film, formed on the other surface of the substrate, opposite to the first multilayer film, and wherein the second multilayer film comprises: a plurality of Si:NH layers, wherein a refraction index of each Si:NH layer is greater than 3.5 in the wavelength range between 800 nm and 1100 nm; and a plurality of second low refraction index layers, stacking with the plurality of Si:NH layers alternatively, wherein a refraction index of each second low refraction index layer is less than 3 in the wavelength range between 800 nm and 1100 nm; wherein the first multilayer film and the second multilayer film are symmetrical to each other with the substrate as a center plane of symmetry; wherein a layer farthest from the substrate in the first multilayer film is the first low refraction index layer, and a layer farthest from the substrate in the second multilayer film is the second low refraction index layer.

16. The infrared band pass filter of claim 15, wherein a material of the first low refraction index layer is selected from Al₂O₃ and SiNOH, and a material of the second low refraction index layer is selected from Al₂O₃ and SiNOH.

17. The infrared band pass filter of claim 15, wherein a material of the layer farthest from the substrate in the first multilayer film is SiNOH, and a material of the layer farthest from the substrate in the second multilayer film is SiNOH.

18. The infrared band pass filter of claim 15, wherein when an incident angle is changed from 0 degrees to 30 degrees, a shift amount of a center wavelength of a pass band of the infrared band pass filter is equal to or less than 11.1 nm.

19. The infrared band pass filter of claim 15, wherein when an incident angle is changed from 0 degrees to 30 degrees, a center wavelength of a pass band of the infrared band pass filter is shifted less than 12 nm.
