

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent
Kind Code
Date of Patent
Inventor(s)

12397507
B2
August 26, 2025
Watanabe; Manabu

Three-dimensional modeling device, method of calibrating three-dimensional modeling device, and method of manufacturing three-dimensional shaped article

Abstract

A three-dimensional modeling device includes a first ejection section configured to eject a first material, a second ejection section configured to eject a second material, a drive section configured to move each of the first ejection section and the second ejection section relatively to a stage, and a control section. The control section executes a calibration process including a first process of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to each other in the calibrating shaped article, a second process of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third process of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion, and the control section executes the first process and the second process once again when the third process is executed in the calibration process.

Inventors: Watanabe; Manabu (Shiojiri, JP)
Applicant: SEIKO EPSON CORPORATION (Tokyo, JP)
Family ID: 1000008781559
Assignee: Seiko Epson Corporation (Tokyo, JP)
Appl. No.: 17/807120
Filed: June 15, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220402213 A1	Dec. 22, 2022

Foreign Application Priority Data

JP 2021-100584 Jun. 17, 2021

Publication Classification

Int. Cl.: B29C64/393 (20170101); B29C64/118 (20170101); B29C64/209 (20170101); B29C64/232 (20170101); B29C64/236 (20170101); B29C64/245 (20170101); B33Y10/00 (20150101); B33Y30/00 (20150101); B33Y50/02 (20150101)

U.S. Cl.:

CPC B29C64/393 (20170801); B29C64/209 (20170801); B29C64/232 (20170801); B29C64/236 (20170801); B29C64/245 (20170801); B33Y10/00 (20141201); B33Y50/02 (20141201); B29C64/118 (20170801); B33Y30/00 (20141201)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
7229144	12/2006	Nielsen et al.	N/A	N/A
10291816	12/2018	Mizes et al.	N/A	N/A
10791245	12/2019	Mizes et al.	N/A	N/A
10994490	12/2020	Matusik	N/A	B29C 64/245
2004/0085377	12/2003	Nielsen et al.	N/A	N/A
2016/0214323	12/2015	Mizes	N/A	H04N 1/40
2019/0230248	12/2018	Mizes et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
105818376	12/2015	CN	N/A
2004-151104	12/2003	JP	N/A
2008-513252	12/2007	JP	N/A
2010-042565	12/2009	JP	N/A
2020-011474	12/2019	JP	N/A
2006/034012	12/2005	WO	N/A

Primary Examiner: Marini; Matthew G

Attorney, Agent or Firm: WORKMAN NYDEGGER

Background/Summary

(1) The present application is based on, and claims priority from JP Application Serial Number 2021-100584, filed Jun. 17, 2021, the disclosure of which is hereby incorporated by reference herein in its entirety.

BACKGROUND

1. Technical Field

(2) The present disclosure relates to a three-dimensional modeling device, a method of calibrating a three-dimensional modeling device, and a method of manufacturing a three-dimensional shaped article.

2. Related Art

(3) In JP-A-2020-011474 (Document 1), there is disclosed a three-dimensional modeling device using a thermal-melting stacking method. This three-dimensional modeling device is provided with a feeding section for feeding a filament material into an ejection section, a feed amount detection section for detecting an amount of feed of the filament material to be fed to the ejection section, and an ejection amount detection section for detecting an amount of ejection of the material ejected from the ejection section, and derives a relationship between the feed amount and the ejection amount to adjust the feed amount so that a desired ejection amount is achieved.

(4) As in Document 1 described above, by adjusting the amount of feed of the material to be fed into the ejection section, it is possible to shape a three-dimensional shaped article with high dimensional accuracy. However, in a three-dimensional modeling device having a modeling nozzle for ejecting a modeling material and a supporting nozzle for ejecting a support material, due to a misalignment in relative position of the supporting nozzle to the modeling nozzle, there is a possibility that the supporting nozzle makes contact with a modeling layer formed of the modeling material to thereby deform the modeling layer, or a possibility that a position of a support layer formed of the support material is shifted to fail to sufficiently support the modeling layer, and thus, the modeling layer deforms during the modeling process. In other words, due to the misalignment of the relative position of the supporting nozzle to the modeling nozzle, there is a possibility that it becomes unachievable to shape the three-dimensional shaped article with high dimensional accuracy. Such a problem as described above occurs not only in the three-dimensional modeling device provided with the modeling nozzle and the supporting nozzle, but also in a three-dimensional modeling device provided with a plurality of modeling nozzles.

SUMMARY

(5) According to a first aspect of the present disclosure, there is provided a three-dimensional modeling device. The three-dimensional modeling device includes a first ejection section configured to eject a first material toward a stage, a second ejection section configured to eject a second material toward the stage, a drive section configured to move each of the first ejection section and the second ejection section relatively to the stage, and a control section configured to control the first ejection section, the second ejection section, and the drive section. The control section executes a calibration process including a first process of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second process of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third process of controlling the drive section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion to thereby adjust a relative position of the second ejection section to the first ejection section. The control section executes the first process and the second process once again when the third process is executed in the calibration process.

(6) According to a second aspect of the present disclosure, there is provided a method of calibrating a three-dimensional modeling device provided with a first ejection section configured to eject a

first material toward a stage, and a second ejection section configured to eject a second material toward the stage. The method of calibrating the three-dimensional modeling device includes a first step of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second step of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third step of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion. When the third step is executed, the first step and the second step are executed once again.

(7) According to a third aspect of the present disclosure, there is provided a method of manufacturing a three-dimensional shaped article. The method of manufacturing a three-dimensional shaped article includes a shaping step of shaping the three-dimensional shaped article using a first ejection section configured to eject a first material toward a stage, and a second ejection section configured to eject a second material toward the stage, and a calibration step of adjusting a relative position of the second ejection section to the first ejection section in advance of the shaping step. The calibration step includes a first step of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second step of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third step of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion. In the calibration step, when the third step is executed, the first step and the second step are executed once again.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIG. 1 is a front view showing a schematic configuration of a three-dimensional modeling device according to a first embodiment.
- (2) FIG. 2 is an explanatory diagram showing a schematic configuration of an ejection section in the first embodiment.
- (3) FIG. 3 is a schematic perspective view showing a configuration at a groove forming surface side of a flat screw.
- (4) FIG. 4 is a top view showing a configuration at a screw-opposed surface side of a barrel.
- (5) FIG. 5 is a flowchart showing a content of a three-dimensional modeling process.
- (6) FIG. 6 is a first explanatory diagram showing a process in which a three-dimensional shaped article is shaped.
- (7) FIG. 7 is a second explanatory diagram showing the process in which the three-dimensional shaped article is shaped.
- (8) FIG. 8 is a third explanatory diagram showing the process in which the three-dimensional shaped article is shaped.
- (9) FIG. 9 is a flowchart showing a content of a calibration process in the first embodiment.
- (10) FIG. 10 is a top view showing a calibrating shaped article for a low-temperature material in the first embodiment.
- (11) FIG. 11 is a cross-sectional view along the line XI-XI in FIG. 10.

(12) FIG. 12 is a top view showing a calibrating shaped article for a high-temperature material in the first embodiment.

(13) FIG. 13 is an explanatory diagram showing an operation history display screen.

(14) FIG. 14 is a top view showing a calibrating shaped article for a low-temperature material in a second embodiment.

(15) FIG. 15 is a front view showing a schematic configuration of a three-dimensional modeling device according to a third embodiment.

(16) FIG. 16 is an explanatory diagram showing a schematic configuration of a three-dimensional modeling device according to a fourth embodiment.

(17) FIG. 17 is an explanatory diagram showing a schematic configuration of an ejection section in a fourth embodiment.

DESCRIPTION OF EXEMPLARY EMBODIMENTS

A. First Embodiment

(18) FIG. 1 is a front view showing a schematic configuration of a three-dimensional modeling device **11** according to a first embodiment. In FIG. 1, there are shown arrows respectively representing X, Y, and Z axes as three coordinate axes perpendicular to each other. The X axis and the Y axis are the coordinate axes along a horizontal plane, and the Z axis is the coordinate axis along a vertical direction. The arrows respectively representing the X, Y, and Z axes are arbitrarily illustrated also in the drawings in FIG. 2 and following diagrams so that the directions pointed by the arrows correspond to those in FIG. 1. In FIG. 1, FIG. 2, and the following diagrams, a direction pointed by the arrow representing the X axis is referred to as a +X direction or “right,” and an opposite direction thereto is referred to as a -X direction or “left” in some cases. A direction pointed by the arrow representing the Y axis is referred to as a +Y direction or “rear,” and an opposite direction thereto is referred to as a -Y direction or “front” in some cases. A direction pointed by the arrow representing the Z axis is referred to as a +Z direction or “upper side,” and an opposite direction thereto is referred to as a -Z direction or “lower side” in some cases. It should be noted that the X axis is referred to as a first axis, and the Y axis is referred to as a second axis in some cases. The X axis is referred to as the second axis, and the Y axis is referred to as the first axis in some cases.

(19) In the present embodiment, the three-dimensional modeling device **11** is provided with a chassis **110**, an operation panel **120**, a first ejection section **100A**, a second ejection section **100B**, a drive section **210**, a stage **220**, and a control section **300**.

(20) The chassis **110** has a modeling space **111** inside. The chassis **110** is provided with, for example, an opening part for communicating the modeling space **111** and the outside with each other. The chassis **110** can be provided with a door or the like for opening and closing the opening part for communicating the modeling space **111** and the outside with each other. In the modeling space **111**, there are arranged a first ejection section **100A**, a second ejection section **100B**, and a stage **220**. An upper surface of the stage **220** is arranged in parallel to the X axis and the Y axis. It should be noted that the stage **220** is referred to as a platen in some cases.

(21) The operation panel **120** is disposed in front of the chassis **110**. The operation panel **120** is formed of, for example, a liquid crystal display or an organic EL display of a touch panel type. The operation panel **120** is coupled to the control section **300**.

(22) The first ejection section **100A** and the second ejection section **100B** are arranged above the stage **220**. In the present embodiment, the first ejection section **100A** and the second ejection section **100B** are arranged horizontally adjacent to each other. When not particularly described, the second ejection section **100B** is the same in configuration as the first ejection section **100A**. In the following description, when describing the first ejection section **100A** and the second ejection section **100B** without particularly discriminating the first ejection section **100A** and the second ejection section **100B** from each other, the first ejection section **100A** and the second ejection section **100B** are simply referred to as ejection sections **100**. The ejection section **100** is referred to

as an ejection head, an injection section, an injection head, an extrusion section, an extrusion head, or simply as a head. It should be noted that in another embodiment, the first ejection section **100A** and the second ejection section **100B** can be arranged adjacent to each other in an anteroposterior direction.

(23) The first ejection section **100A** has a first nozzle **60A**, and the second ejection section **100B** has a second nozzle **60B**. The first ejection section **100A** ejects a first material from the first nozzle **60A** toward the stage **220**, and the second ejection section **100B** ejects a second material from the second nozzle **60B** toward the stage **220**. The term “ejection” mentioned here includes the meaning of “injection” or “extrusion.” In the following description, when describing the first material and the second material without particularly discriminating the first material and the second material from each other, the first material and the second material are simply referred to as materials. When describing the first nozzle **60A** and the second nozzle **60B** without particularly discriminating the first nozzle **60A** and the second nozzle **60B** from each other, the first nozzle **60A** and the second nozzle **60B** are simply referred to as nozzles **60**. The nozzle **60** is referred to as a nozzle chip or a chip in some cases. The first nozzle **60A** and the second nozzle **60B** can be nozzles the same in type as each other, or can also be nozzles different in type from each other. For example, the first nozzle **60A** and the second nozzle **60B** can be different in nozzle aperture from each other.

(24) In the present embodiment, the first material is a modeling material for forming a product portion of a three-dimensional shaped article, and the second material is a support material for forming a support portion for supporting the product portion in the middle of the modeling. As the modeling material, it is possible to use, for example, a material obtained by combining ABS resin, polylactic acid (PLA), polyetherimide (PEI), or nylon 12 and carbon fiber with each other. As the support material, there can be used, for example, HIPS (High Impact Polystyrene) or polyvinyl alcohol (PVA). It should be noted that in another embodiment, it is possible for the first material and the second material to be modeling materials. In this case, it is possible for the first material and the second material to be the modeling materials the same in type as each other, or it is possible for the first material and the second material to be the modeling materials different in type from each other.

(25) The drive section **210** changes relative positions of the first ejection section **100A** and the second ejection section **100B** with respect to the stage **220**. In the present embodiment, the drive section **210** has a first drive section **211** for moving the stage **220** along the Z axis, and a second drive section **212** for moving the first ejection section **100A** and the second ejection section **100B** along the X axis and the Y axis. The first drive section **211** is configured as an elevating device, and is provided with a motor for moving the stage **220** along the Z axis. The second drive section **212** is configured as a horizontal carrier device, and is provided with a motor for translating the first ejection section **100A** and the second ejection section **100B** along the X axis, and a motor for translating them along the Y axis. Each of the motors is driven under the control by the control section **300**. It should be noted that in another embodiment, there can be adopted a configuration in which the first drive section **211** moves the stage **220** along the X axis and the Y axis, and the second drive section **212** moves the first ejection section **100A** and the second ejection section **100B** along the Z axis. It is possible to adopt a configuration in which the first drive section **211** is not provided with the drive section **210**, and the second drive section **212** moves the first ejection section **100A** and the second ejection section **100B** along the three axes of X, Y, and Z. It is possible to adopt a configuration in which the second drive section **212** is not provided with the drive section **210**, and the first drive section **211** moves the stage **220** along the three axes of X, Y, and Z.

(26) In the present embodiment, the drive section **210** further has a third drive section **213** for changing a relative position of the second ejection section **100B** with respect to the first ejection section **100A**. The third drive section **213** is disposed between the second ejection section **100B** and the second drive section **212**, and moves the second ejection section **100B** along the three axes

of X, Y, and Z. The third drive section **213** is configured by combining electric actuators driven under the control by, for example, the control section **300**. It should be noted that in another embodiment, the third drive section **213** is disposed between the first ejection section **100A** and the second drive section **212**, and moves the first ejection section **100A** along the three axes of X, Y, and Z. When the second drive section **212** is not provided, the third drive section **213** can be disposed between the first ejection section **100A** or the second ejection section **100B** and the chassis **110**.

(27) The control section **300** is formed of a computer provided with at least one processor, a memory, and an input/output interface for performing input/output of a signal with the outside. The control section **300** controls the first ejection section **100A**, the second ejection section **100B**, and the drive section **210**. In the present embodiment, it is possible for the control section **300** to execute a three-dimensional modeling process and a calibration process described later by the processor executing a program or a command retrieved in the memory. It should be noted that it is also possible for the controller **300** to be formed of a combination of a plurality of circuits instead of the computer.

(28) FIG. 2 is an explanatory diagram showing a schematic configuration of the ejection section **100** in the present embodiment. The ejection section **100** is provided with a material housing section **20**, a plasticizing mechanism **30**, and the nozzle **60** described above.

(29) In the material housing section **20**, there is housed the material in the form of a pellet or a powder. In the present embodiment, the material housing section **20** is formed of a hopper. A feed path **22** for communicating the material housing section **20** and the plasticizing mechanism **30** to each other is disposed below the material housing section **20**. The material housed in the material housing section **20** is fed to the plasticizing mechanism **30** via the feed path **22**.

(30) The plasticizing mechanism **30** plasticizes at least a part of the material fed from the material housing section **20** to feed the material thus plasticized to the nozzle **60**. The term “plasticization” is a concept including melting, and means changing an object from a solid state to a state having fluidity. Specifically, in the case of a material in which glass transition occurs, the plasticization means that the temperature of the material is made equal to or higher than the glass-transition point. In the case of a material in which the glass transition does not occur, the plasticization means that the temperature of the material is made equal to or higher than a melting point.

(31) The plasticizing mechanism **30** is provided with a material carrying mechanism **40** and a heating block **90**. The material carrying mechanism **40** has a function of carrying the material fed via the feed path **22**. In the present embodiment, the material carrying mechanism **40** is provided with a screw case **31**, a drive motor **32**, and a flat screw **41**. It should be noted that the flat screw **41** is referred to as a screw or a scroll in some cases.

(32) In the screw case **31**, there is housed the flat screw **41**. A bottom surface of the screw case **31** is provided with an opening part. To the bottom surface of the screw case **31**, there is fixed a barrel **50** described later so as to close the opening part described above. In a space surrounded by the screw case **31** and the barrel **50**, there is arranged the flat screw **41**.

(33) The drive motor **32** is fixed to an upper surface of the screw case **31**. An output shaft of the drive motor **32** is coupled to the flat screw **41** so as to penetrate the screw case **31**. The output shaft of the drive motor **32** can directly be coupled to the flat screw **41**, or can also be coupled to the flat screw **41** via a reduction gear. The drive motor **32** is driven under the control by the control section **300**.

(34) The flat screw **41** has a substantially cylindrical shape having a height in a direction along a central axis RX smaller than the diameter. The bottom surface of the flat screw **41**, namely a surface opposed to the barrel **50**, is provided with a groove forming surface **42**. On the groove forming surface **42**, there are formed screw grooves **45**. A more specific configuration at the groove forming surface side will be described later. Due to the torque generated by the drive motor **32**, the flat screw **41** rotates around the central axis RX. By the flat screw **41** rotating, there is carried the

material which has been fed from the material housing section **20** to an area between the flat screw **41** and the barrel **50**.

(35) The heating block **90** has a function of heating the material carried by the material carrying mechanism **40**. In the present embodiment, the heating block **90** is provided with the barrel **50**, a heater **58**, and a case part **91**.

(36) The barrel **50** has a screw-opposed surface **52** opposed to the groove forming surface **42** of the flat screw **41**. At the center of the screw-opposed surface **52**, there is disposed an opening part of a communication hole **56**. The opening part of the communication hole **56** provided to the screw-opposed surface **52** is arranged on an extended line of the central axis RX of the flat screw **41**. The communication hole **56** penetrates the barrel **50**.

(37) In the present embodiment, the heater **58** is arranged inside the barrel **50**. The heater **58** is controlled by the control section **300**, and is heated to a melting temperature for plasticizing the material. The melting temperature differs by a type of the material to be used, and is, for example, no lower than the glass-transition point or the melting point of the material. When the material is ABS resin, the melting temperature is set to, for example, a temperature no lower than about 110° C. which is the glass-transition point of ABS resin. It should be noted that in the present embodiment, the heater **58** can be arranged outside the barrel **50**.

(38) The case part **91** is arranged so as to cover a surface at an opposite side to the screw-opposed surface **52** of the barrel **50**, namely a bottom surface of the barrel **50**. The case part **91** is provided with a through hole **94**. The through hole **94** of the case part **91**, and a lower end part of the communication hole **56** of the barrel **50** constitute an attaching hole **80** for detachably fixing the nozzle **60**. For example, a side surface of the nozzle **60** is provided with an external thread, the attaching hole **80** is provided with an internal thread, and the nozzle **60** is fixed to the attaching hole **80** using the external thread and the internal thread.

(39) The nozzle **60** is fixed to the attaching hole **80** so as to aim the tip portion of the nozzle **60** downward. In a rear end portion of the nozzle **60**, there is disposed a nozzle inflow port **65** communicated with the communication hole **56**. In a tip portion of the nozzle **60**, there is disposed a nozzle opening **63** for ejecting the plasticized material. The nozzle **60** is provided with a nozzle flow channel **61** for communicating the nozzle inflow port **65** and the nozzle opening **63** with each other. The nozzle **60** ejects the material inflows into the nozzle flow channel **61** from the nozzle inflow port **65** from the nozzle opening **63** toward the stage **220**.

(40) In the present embodiment, the nozzle **60** is provided with a shield **68** shaped like a flange. The shield is disposed so as to project outward from the side surface of the nozzle **60**. The shield **68** is arranged between the nozzle opening **63** and the heating block **90** in the Z axis. By disposing the shield **68**, it is possible to prevent the heat from the heating block **90** from being transferred to the material stacked on the stage **220**.

(41) FIG. 3 is a schematic perspective view showing a configuration at the groove forming surface **42** side of the flat screw **41**. In FIG. 3, the position of the central axis RX of the flat screw **41** is represented by the dashed-dotted line. As described above, the groove forming surface **42** is provided with the grooves **45**. A screw central portion **47** as a central portion of the groove forming surface **42** of the screw **41** is formed as a recess to which one ends of the grooves **45** are coupled. The screw central portion **47** is opposed to the communication hole **56** of the barrel **50**. The screw central portion **47** crosses the central axis RX.

(42) The screw grooves **45** of the flat screw **41** each constitute a so-called scroll groove. The screw grooves **45** each extend in a vertical manner from the screw central portion **47** toward an outer circumference of the flat screw **41** so as to draw an arc. The screw grooves **45** can also be formed so as to extend forming an involute-curved shape or a spiral shape. The groove forming surface **42** is provided with protruding line parts **46** each constituting a sidewall part of the screw groove **45**, and extending along each of the screw grooves **45**. The screw grooves **45** each continue to a material introduction port **44** formed on a side surface **43** of the flat screw **41**. The material

introduction port **44** is a portion for receiving the material fed via the feed path **22** of the material housing section **20**.

(43) In FIG. **3**, there is shown an example of the flat screw **41** having the three screw grooves **45** and the three protruding line parts **46**. The number of the screw grooves **45** and the number of the protruding line parts **46** provided to the flat screw **41** are not limited to three, and it is possible to disposed just one screw groove **45**, or it is possible to dispose two or more screw grooves **45**. Further, in FIG. **3**, there is illustrated an example of the flat screw **41** having the material introduction ports **44** formed at three places. The number of the material introduction ports **44** provided to the flat screw **41** is not limited to three, and the material introduction port **44** can be disposed at just one place, or can also be disposed at two or more places.

(44) FIG. **4** is a top view showing a configuration at the screw-opposed surface **52** side of the barrel **50**. As described above, at the center of the screw-opposed surface **52**, there is formed the communication hole **56**. On the periphery of the communication hole **56** in the screw-opposed surface **52**, there is formed a plurality of guide grooves **54**. Each of the guide grooves **54** is coupled to the communication hole **56** at one end, and extends in a vertical manner from the communication hole **56** toward the outer circumference of the screw-opposed surface **52**. Each of the guide grooves **54** has a function of guiding the material to the communication hole **56**. It should be noted that the one ends of the guide grooves **54** are not required to be coupled to the communication hole **56**. Further, it is not required to provide the guide grooves **54** to the barrel **50**.

(45) FIG. **5** is a flowchart showing a content of a three-dimensional modeling process in the present embodiment. The processing is started when the control section **300** has received a predetermined operation from the user. The processing is started when, for example, a start button for the three-dimensional modeling process displayed in the operation panel **120** is tapped.

(46) First, in the step **S110**, the control section **300** obtains modeling data. The control section **300** obtains the modeling data from, for example, an external computer or a recording medium. The modeling data includes first tool path data representing a movement path of the first nozzle **60A** and second tool path data representing a movement path of the second nozzle **60B** when forming layers constituting the three-dimensional shaped article. First ejection amount data representing an amount of ejection of the first material to be ejected from the first nozzle **60A** is associated with the first tool path data. Second ejection amount data representing an amount of ejection of the second material to be ejected from the second nozzle **60B** is associated with the second tool path data.

(47) Then, in the step **S120**, the control section **300** controls the first ejection section **100A**, the second ejection section **100B**, and the drive section **210** in accordance with the modeling data to thereby form a layer having at least one of a product portion which is formed of the modeling material ejected from the first nozzle **60A** and a support portion formed of a support material ejected from the second nozzle **60B** on the stage **220**.

(48) In the step **S130**, the control section **300** determines whether or not the modeling of all of the layers is completed. It is possible for the control section **300** to determine whether or not the modeling of all of the layers is completed using the modeling data. When it has not been determined that the modeling of all of the layers has been completed in the step **S130**, the control section **300** returns the process to the step **S120** to further model a layer on the layer. When it has been determined in the step **S130** that the modeling of all of the layers has been completed, the control section **300** terminates this processing.

(49) FIG. **6** is a first explanatory diagram showing a process in which a three-dimensional shaped article **OB** is shaped. FIG. **7** is a second explanatory diagram showing a process in which the three-dimensional shaped article **OB** is shaped. FIG. **8** is a third explanatory diagram showing a process in which the three-dimensional shaped article **OB** is shaped. In FIG. **6** through FIG. **8**, there is shown an example of a process in which the three-dimensional shaped article **OB** is shaped using the three-dimensional modeling process described above.

(50) In the step **S120** of the three-dimensional modeling process, the control section **300** controls

the second drive section **212** to eject the modeling material from the first nozzle **60A** while moving the first nozzle **60A** along the first tool path to thereby form a modeling layer ML made of the modeling material as shown in, for example, FIG. **6**, and then controls the second drive section **212** to eject the support material from the second nozzle **60B** while moving the second nozzle **60B** along the second tool path to thereby form a support layer SL made of the support material as shown in FIG. **7**. After the step **S130**, in the step **S120**, the control section **300** controls once again, for example, the first drive section **211** to move down the stage **220** as much as the thickness of the modeling layer ML, and then, controls the second drive section **212** to eject the modeling material from the first nozzle **60A** while moving the first nozzle **60A** along the first tool path to thereby further form the modeling layer ML on the support layer SL and the modeling layer ML as shown in FIG. **8**.

(51) The control section **300** repeats the step **S120** and the step **S130** to stack the modeling layers ML and the support layers SL on one another to thereby shape the three-dimensional shaped article OB. After the three-dimensional modeling process is terminated, the product portion formed of the modeling layer ML and the support portion formed of the support layer SL out of the three-dimensional shaped article OB are separated from each other.

(52) The larger the number of times of execution of the three-dimensional modeling process becomes, the higher the degree of deterioration of the first nozzle **60A** and the second nozzle **60B** becomes. When the degree of deterioration of the first nozzle **60A** and the second nozzle **60B** reaches a predetermined degree of deterioration, there is a possibility that it becomes unachievable to shape the three-dimensional shaped article OB with high dimensional accuracy, and therefore, the first nozzle **60A** and the second nozzle **60B** are replaced. When the replacement of the first nozzle **60A** and the second nozzle **60B** is performed, a relative position of the second nozzle **60B** to the first nozzle **60A** is displaced in some cases due to an installation error of the first nozzle **60A** and the second nozzle **60B** or the like. When the relative position of the second nozzle **60B** to the first nozzle **60A** is displaced, there is a possibility that the modeling layer ML is deformed due to the second nozzle **60B** making contact with the modeling layer ML during the three-dimensional modeling process, or a possibility that the modeling layer ML cannot be supported by the support layer SL and is deformed due to the relative position of the support layer SL to the modeling layer ML being displaced. In a method of manufacturing the three-dimensional shaped article OB according to the present embodiment, when at least one of the first nozzle **60A** and the second nozzle **60B** is replaced, it is possible to adjust the relative position of the second nozzle **60B** to the first nozzle **60A** by executing a calibration process in advance of the three-dimensional modeling process.

(53) FIG. **9** is a flowchart showing a content of the calibration process in the present embodiment. FIG. **10** is a top view showing a calibrating shaped article CM1 shaped in accordance with calibrating modeling data for a low-temperature material in the calibration process in the present embodiment. FIG. **11** is a cross-sectional view along the line XI-XI in FIG. **10**. FIG. **12** is a top view showing a calibrating shaped article CM2 shaped in accordance with calibrating modeling data for a high-temperature material in the calibration process in the present embodiment.

(54) As shown in FIG. **9**, the calibration process is started when the control section **300** has received a predetermined operation from the user. The processing is started when, for example, a start button for the calibration process displayed in the operation panel **120** is tapped.

(55) First, in the step **S210**, the control section **300** reads material data representing a type of the first material to be ejected from the first nozzle **60A**, and a type of the second material to be ejected from the second nozzle **60B**. In the present embodiment, the material data is stored in advance in the memory of the control section **300**. The control section **300** reads the material data from the memory. The type of the first material and the type of the second material are input by the user via, for example, the operation panel **120**.

(56) Then, in the step **S220**, the control section **300** obtains area data representing an area on the

stage **220** for shaping the calibrating shaped article **CM1** shown in FIG. **10** or the calibrating shaped article **CM2** shown in FIG. **12**. The calibrating shaped articles **CM1**, **CM2** mean three-dimensional shaped articles to be used for the calibration of the three-dimensional modeling device **11**. The calibrating shaped articles **CM1**, **CM2** are referred to as shaped articles for the calibration, or calibration models in some cases. In the present embodiment, an area on the stage **220** for shaping the calibrating shaped articles **CM1**, **CM2** is designated by the user via the operation panel **120**. The control section **300** obtains the area data representing the area on the stage **220** designated via the operation panel **120**. It should be noted that in another embodiment, it is possible for the control section **300** to shape the calibrating shaped articles **CM1**, **CM2** in an area set in advance on the stage **220** instead of the area designated by the user.

(57) In the step **S230**, the control section **300** reads the calibrating modeling data for shaping the calibrating shaped articles **CM1**, **CM2**. In the present embodiment, the calibrating modeling data for shaping the calibrating shaped article **CM1** using the low-temperature material as a material having the melting temperature lower than a predetermined temperature, and the calibrating modeling data for shaping the calibrating shaped article **CM2** using the high-temperature material as a material having the melting temperature no lower than the predetermined temperature are stored in advance in the memory of the control section **300**. The calibrating modeling data corresponding to the type of the material represented by the material data read in the step **S210** is read by the control section **300** from the memory. In the present embodiment, the control section **300** reads the calibrating modeling data for the low-temperature material when shaping the calibrating shaped article **CM1** using the modeling material such as ABS resin or PLA. The control section **300** reads the calibrating modeling data for the high-temperature material when shaping the calibrating shaped article **CM2** using, for example, the modeling material obtained by combining polyetherimide (PEI) or nylon 12 with carbon fibers.

(58) In the step **S240**, the control section **300** controls the first ejection section **100A**, the second ejection section **100B**, and the drive section **210** in accordance with the calibrating modeling data read in the step **S230** to thereby shape the calibrating modeling articles **CM1**, **CM2** in the area on the stage **220** represented by the area data.

(59) As shown in FIG. **10**, the calibrating shaped article **CM1** shaped in accordance with the calibrating modeling data for the low-temperature material is configured so as to have a frame-like quadrangular shape in a top view. The calibrating shaped article **CM1** has a left portion **LP** corresponding to a left side of the quadrangular shape, a right portion **RP** corresponding to a right side of the quadrangular shape, a front portion **FP** corresponding to a bottom side of the quadrangular shape, and a back portion **BP** corresponding to a top side of the quadrangular shape.

(60) In the present embodiment, the left portion **LP**, the right portion **RP**, the front portion **FP**, and the back portion **BP** each have five first portions **P1**, five second portions **P2**, a single third portion **P3**, and a single fourth portion **P4**. It should be noted that the number of the first portions **P1** provided to each of the portions **LP**, **RP**, **FP**, and **BP** is not limited to five, and is only required to, for example, no smaller than two. The number of the second portions **P2** provided to each of the portions **LP**, **RP**, **FP**, and **BP** is not limited to five, and is only required to, for example, no smaller than two. It is preferable for the number of the first portions **P1** and the number of the second portions **P2** to be the same as each other.

(61) In the following descriptions, a term of “left,” “right,” “front,” or “back” is attached at the head of the name of each of the terms of first portion **P1**, second portion **P2**, third portion **P3**, and fourth portion **P4**, and a character of “L,” “R,” “F,” or “B” is attached at the tail of the reference symbol thereof in some cases. For example, the first portion **P1** provided to the left portion **LP** is referred to as a left first portion **P1L** in some cases, the first portion **P1** provided to the right portion **RP** is referred to as a right first portion **P1R** in some cases, the second portion **P2** provided to the front portion **FP** is referred to as a front second portion **P2F** in some cases, and the second portion **P2** provided to the back portion **BP** is referred to as a back second portion **P2B** in some cases.

(62) As described above, the left portion LP has the five left first portions P1L, the five left second portions P2L, and the single left third portion P3L, and the single left fourth portion P4L. The five left first portions P1L are arranged side by side along the Y axis. Each of the left first portions P1L is configured to be shaped like a straight line parallel to the Y axis. In the present embodiment, each of the left first portions P1L is formed of a single first material ejected in the form of a line from the first nozzle 60A. The left first portions P1L are the same in length as each other. The left first portions P1L are arranged so that the further the left first portion P1L is shifted toward the -Y direction, the further that left first portion P1L is shifted toward the -X direction. The positions in the X axis of the left first portions P1L adjacent to each other are different from each other as much as a predetermined distance. In the present embodiment, the positions in the X axis of the left first portions P1L adjacent to each other are different from each other as much as 0.05 millimeter. It should be noted that in another embodiment, the left first portions P1L can be arranged so that the further the left first portion P1L is shifted toward the -Y direction, the further that left first portion P1L is shifted toward the +X direction. In the present embodiment, the positions in the X axis of the left first portions P1L adjacent to each other can be different from each other as much as, for example, 0.10 millimeter instead of 0.05 millimeter.

(63) The five left second portions P2L are arranged side by side along the Y axis. Each of the left second portions P2L is arranged at the +X direction side with respect to corresponding one of the left first portions P1L. The left second portions P2L are configured to be shaped like straight lines parallel to the Y axis, in other words, parallel to the respective left first portions P1L. In the present embodiment, each of the left second portions P2L is formed of a single first material ejected in the form of a line from the first nozzle 60A. The left second portions P2L are the same in length as the respective left first portions P1L. The five left second portions P2L are each arranged at a predetermined distance from the left first portion P1L the same in position in the Y axis as that left second portion P2L. Distances between the five left second portions P2L from the corresponding left first portions P1L the same in position in the Y axis as the five left second portions P2L are the same as each other. For example, the left second portion P2L disposed at the farthest to the +Y direction side is disposed at a predetermined distance from the left first portion P1L disposed at the farthest to the +Y direction side. The left second portion P2L disposed at the second farthest to the +Y direction side is disposed at a predetermined distance from the left first portion P1L disposed at the second farthest to the +Y direction side, and the predetermined distance is the same as the distance between the left second portion P2L disposed at the farthest to the +Y direction side and the left first portion P1L disposed at the farthest to the +Y direction side.

(64) The left third portion P3L is disposed between the left first portions P1L and the left second portions P2L. The left third portion P3L is configured to be shaped like a straight line parallel to the Y axis. In the present embodiment, the left third portion P3L is formed of a single second material ejected in the form of a line from the second nozzle 60B. The length of the left third portion P3L is longer than the length of the left first portion P1L, and the length of the left second portion P2L. An end portion at the +Y direction side of the left third portion P3L is disposed at the +Y direction side with respect to an end portion at the +Y direction side of the left first portion P1L disposed at the farthest to the +Y direction side out of the five left first portions P1L. An end portion at the -Y direction side of the left third portion P3L is disposed at the -Y direction side with respect to an end portion at the -Y direction side of the left first portion P1L disposed at the farthest to the -Y direction side out of the five left first portions P1L.

(65) The left fourth portion P4L is arranged at the +X direction side with respect to the left second portions P2L. The left fourth portion P4L is configured to be shaped like a straight line parallel to the Y axis. In the present embodiment, the left fourth portion P4L is formed of a single second material ejected in the form of a line from the second nozzle 60B.

(66) As described above, the right portion RP has the right first portions P1R, the right second portions P2R, the right third portion P3R, and the right fourth portion P4R. The right portion RP is

configured so as to be bilaterally symmetric with the left portion LP. In other words, the right first portions P1R are arranged so that the farther the right first portion P1R is shifted toward the -Y direction side, the farther that right first portion P1R is shifted toward the +X direction side, and the right second portions P2R are arranged so that the farther the right second portion P2R is shifted toward the -Y direction side, the farther that right second portion P2R is shifted toward the +X direction side. The right third portion P3R is disposed between the right first portions P1R and the right second portions P2R. The right fourth portion P4R is arranged at the -X direction side with respect to the right second portions P2R.

(67) As described above, the front portion FP has the five front first portions P1F, the five front second portions P2F, and the single front third portion P3F, and the single front fourth portion P4F. The front portion FP has substantially the same configuration as the configuration of the left portion LP which is rotated counterclockwise as much as 90 degrees when viewed downward from above. In other words, the front first portions P1F, the front second portions P2F, the front third portion P3F, and the front fourth portion P4F are arranged in parallel to the X axis. The front first portions P1F are arranged so that the farther the front first portion P1F is shifted toward the +X direction side, the farther that front first portion P1F is shifted toward the -Y direction side, and the front second portions P2F are arranged so that the farther the front second portion P2F is shifted toward the +X direction side, the farther that front second portion P2F is shifted toward the -Y direction side. The front third portion P3F is disposed between the front first portions P1F and the front second portions P2F. The front fourth portion P4F is arranged at the +Y direction side with respect to the front second portions P2F.

(68) The back portion BP has the back first portions P1B, the back second portions P2B, the back third portion P3B, and the back fourth portion P4B. The back portion BP is configured so as to be longitudinally symmetric with the front portion FP. In other words, the back first portions P1B are arranged so that the farther the back first portion P1B is shifted toward the +X direction side, the farther that back first portion P1B is shifted toward the +Y direction side, and the back second portions P2B are arranged so that the farther the back second portion P2B is shifted toward the +X direction side, the farther that back second portion P2B is shifted toward the +Y direction side. The back third portion P3B is disposed between the back first portions P1B and the back second portions P2B. The back fourth portion P4B is arranged at the -Y direction side with respect to the back second portions P2B.

(69) In the present embodiment, by the end portions of the third portions P3L, P3R, P3F, and P3B being coupled to each other, the four third portions P3L, P3R, P3F, and P3B are formed to have a square frame-like shape. By the end portions of the fourth portions P4L, P4R, P4F, and P4B being coupled to each other, the four fourth portions P4L, P4R, P4F, and P4B are formed to have a square frame-like shape.

(70) As shown in FIG. 11, in the present embodiment, the first portions P1, the second portions P2, the third portions P3, and the fourth portions P4 are each formed of a single layer. In the following description, a distance between the first portion P1 and the third portion P3 arranged side by side are referred to as a first distance W1, and a distance between the second portion P2 and the third portion P3 arranged side by side is referred to as a second distance W2. In the present embodiment, the second tool path for shaping the third portion P3 is disposed at the midpoint between the first tool path for shaping the first portion P1 and the first tool path for shaping the second portion P2 at the position of the left first portion P1L disposed at the farthest to the +Y direction side, the position of the right first portion P1R disposed at the farthest to the +Y direction side, the position of the front first portion P1F disposed at the farthest to the -X direction side, and the position of the back first portion P1B disposed at the farthest to the -X direction side. Therefore, when no displacement occurs in the relative position between the nozzles 60A, 60B, the first distances W1 and the second distances W2 become equal to each other at each of the positions described above.

(71) As shown in FIG. 10, in the present embodiment, in an area on the stage 220 represented by

the area data, there are shaped offset amount displaying shaped articles **DM1**, unit displaying shaped articles **DM2**, and a material displaying shaped article **DM3** together with the calibrating shaped article **CM1**.

(72) The offset amount displaying shaped articles **DM1** are arranged adjacent to the first portions **P1**, respectively. The shapes of the offset amount displaying shaped articles **DM1** represent absolute values of offset amounts of the first portions **P1** disposed adjacent to the offset amount displaying shaped articles **DM1**, respectively. The offset amount of the first portion **P1** means a shift amount of the first portion **P1** from a reference position.

(73) In the example shown in FIG. **10**, the offset amount displaying shaped articles **DM1** are arranged at the positions adjacent to the left first portions **P1L**, and the positions adjacent to the back first portions **P1B**, respectively. The offset amount displaying shaped articles **DM1** arranged adjacent to the left first portions **P1L** represent the offset amounts of the left first portions **P1L** in the X axis, respectively, taking the position of the left first portion **P1L** disposed at the farthest to the +Y direction side as a reference position. The offset amounts of the left first portions **P1L** in the X axis correspond to a variation in position of the first nozzle **60A** in the X axis when shaping the respective left first portions **P1L**. The offset amount displaying shaped articles **DM1** arranged adjacent to the left first portions **P1L** respectively represent numerals of “0,” “0.05,” “0.1,” “0.15,” and “0.2” in this order from the +Y direction side.

(74) The offset amount displaying shaped articles **DM1** arranged adjacent to the back first portions **P1B** represent the offset amounts of the back first portions **P1B** in the Y axis, respectively, taking the position of the back first portion **P1B** disposed at the farthest to the −X direction side as a reference position. The offset amounts of the back first portions **P1B** in the Y axis correspond to a variation in position of the first nozzle **60A** in the Y axis when shaping the respective back first portions **P1B**. The offset amount displaying shaped articles **DM1** arranged adjacent to the back first portions **P1B** respectively represent numerals of “0,” “0.05,” “0.1,” “0.15,” and “0.2” in this order from the −X direction side.

(75) In the present embodiment, the three-dimensional modeling device **11** has a metric system mode of representing a length in the metric system, and an Imperial system mode of representing a length in the Imperial system as operation modes. In the metric system mode, the offset amounts represented by the offset amount displaying shaped articles **DM1** are represented in the metric system, and in the Imperial system mode, the offset amounts represented by the offset amount displaying shaped articles **DM1** are represented in the Imperial system.

(76) The unit displaying shaped articles **DM2** are each arranged in the vicinity of the offset amount displaying shaped article **DM1**. The shape of the unit displaying shaped article **DM2** represents the unit of the offset amount, namely the unit of a value represented by the offset amount displaying shaped article **DM1**. In the example shown in FIG. **10**, the shape of the unit displaying shaped article **DM2** represents characters of “mm.” The characters of “mm” represent the fact that the unit of the values represented by the offset amount displaying shaped articles **DM1** is millimeter. In the metric system mode, the unit represented by the unit displaying shaped article **DM2** is represented in the metric system, and in the Imperial system mode, the unit represented by the unit displaying shaped article **DM2** is represented in the Imperial system.

(77) The shape of the material displaying shaped article **DM3** represents the type of the first material and the type of the second material. In the example shown in FIG. **10**, the shape of the material displaying shaped article **DM3** represents characters of “ABS/HIPS.” The characters of “ABS/HIPS” represent the fact that the type of the first material is ABS resin, and the type of the second material is HIPS.

(78) In the present embodiment, the offset amount displaying shaped articles **DM1**, the unit displaying shaped articles **DM2**, and the material displaying shaped article **DM3** are formed of the first material. It should be noted that in another embodiment, at least one of the offset amount displaying shaped articles **DM1**, the unit displaying shaped articles **DM2**, and the material

displaying shaped article DM3 can be formed of the second material.

(79) FIG. 12 is a top view showing the calibrating shaped article CM2 shaped in accordance with the calibrating modeling data for the high-temperature material. The shape of the calibrating shaped article CM2 shaped in accordance with the calibrating modeling data for the high-temperature material is different from the shape of the calibrating shaped article CM1 shaped in accordance with the calibrating modeling data for the low-temperature material shown in FIG. 10. Specifically, the calibrating shaped article CM2 shaped in accordance with the calibrating modeling data for the high-temperature material is different from the calibrating shaped article CM1 shaped in accordance with the calibrating modeling data for the low-temperature material in the point that the right first portions P1R, the right second portions P2R, the right third portion P3R, the back first portions P1B, the back second portions P2B, and the back third portion P3B are not provided.

(80) In the present embodiment, the size of the calibrating shaped article CM2 shaped in accordance with the calibrating modeling data for the high-temperature material is larger than the size of the calibrating shaped article CM1 shaped in accordance with the calibrating modeling data for the low-temperature material. Specifically, the length along the X axis and the length along the Y axis of the calibrating shaped article CM2 shaped in accordance with the calibrating modeling data for the high-temperature material are longer than the length along the X axis and the length along the Y axis of the calibrating shaped article CM1 shaped in accordance with the calibrating modeling data for the low-temperature material, respectively.

(81) In the present embodiment, in the step S240 shown in FIG. 9, the control section 300 shapes the calibrating shaped articles CM1, CM2, and then, shapes the offset amount displaying shaped articles DM1, the unit displaying shaped articles DM2, and the material displaying shaped article DM3 in this order. It should be noted that the order in which the calibrating shaped articles CM1, the offset amount displaying shaped articles DM1, the unit displaying shaped article DM2, and the material displaying shaped article DM3 are shaped is not limited to the order described above, and any orders can be adopted. For example, it is possible to shape the calibrating shaped articles CM1, CM2 after the offset amount displaying shaped articles DM1, the unit displaying shaped articles DM2, and the material displaying shaped article DM3 are shaped in this order. It is possible for the control section 300 not to shape at least one of the offset amount displaying articles DM1, the unit displaying shaped articles DM2, and the material displaying shaped article DM3 in the calibration process.

(82) In the present embodiment, when shaping the calibrating shaped articles CM1, CM2, the control section 300 ejects the first material from the first nozzle 60A while moving the first ejection section 100A and the second ejection section 100B using the second drive section 212 to thereby shape the first portions P1 and the second portions P2 on the stage 220 in this order, and then, ejects the second material from the second nozzle 60B while moving the first ejection section 100A and the second ejection section 100B using the second drive section 212 to thereby shape the third portions P3 and the fourth portions P4 on the stage 220 in this order. The control section 300 makes positions of the first nozzle 60A in the X axis when shaping the left first portions P1L, the left second portions P2L, the right first portions P1R, and the right second portions P2R different from each other using the second drive section 212 to thereby make the positions of the left first portions P1L, the left second portions P2L, the right first portions P1R, and the right second portions P2R in the X axis different from each other. The control section 300 makes positions of the first nozzle 60A in the Y axis when shaping the front first portions P1F, the front second portions P2F, the back first portions P1B, and the back second portions P2B different from each other using the second drive section 212 to thereby make the positions of the front first portions P1F, the front second portions P2F, the back first portions P1B, and the back second portions P2B in the Y axis different from each other. It should be noted that the order in which the first portions P1, the second portions P2, the third portions P3, and the fourth portions P4 are shaped is not limited to the order described above, and any orders can be adopted. For example, it is possible for the control section 300 to

shape the fourth portions **P4** after shaping the third portions **P3**, and further shape the first portions **P1** and the second portions **P2**. Ejecting the first material from the first nozzle **60A** to thereby shape the first portions **P1** and the second portions **P2** is referred to as a first process, a first step of a calibration method of the three-dimensional modeling device **11**, or a first step of a calibration step in some cases, and ejecting the second material from the second nozzle **60B** to thereby shape the third portions **P3** is referred to as a second process, a second step of the calibration method of the three-dimensional modeling device **11**, or a second step of the calibration step in some cases.

(83) As shown in FIG. 9, in the step **S250**, the control section **300** obtains an X correction value and a Y correction value. In the present embodiment, the X correction value and the Y correction value are input by the user to the operation panel **120**. It is possible to input the X correction value and the Y correction value to the operation panel **120** in terms of 0.05 millimeter (0.002 inch). The control section **300** obtains the X correction value and the Y correction value input to the operation panel **120**. In the present embodiment, first, the user observes the calibrating shaped articles **CM1**, **CM2** with, for example, a magnifying glass to thereby identify a position where an absolute value of a difference between the first distance **W1** and the second distance **W2** in the X axis is the smallest, and a position where an absolute value of a difference between the first distance **W1** and the second distance **W2** in the Y axis is the smallest. Then, the user refers to the offset amounts represented by the offset amount displaying shaped articles **DM1** to figure out the offset amount of the first portion **P1** in the X axis at the position where the absolute value of the difference between the first distance **W1** and the second distance **W2** in the X axis is the smallest, and the offset amount of the first portion **P1** in the Y axis at the position where the absolute value of the difference between the first distance **W1** and the second distance **W2** in the Y axis is the smallest. Subsequently, the user inputs a value obtained by multiplying the offset amount of the first portion **P1** in the X axis at the position thus identified by “-1” to the operation panel **120** as the X correction value, and inputs a value obtained by multiplying the offset amount of the first portion **P1** in the Y axis by “-1” to the operation panel **120** as the Y correction value.

(84) In the example shown in FIG. 10, the position where the absolute value of the difference between the first distance **W1** and the second distance **W2** is the smallest in the X axis is the position of the left first portion **P1L** at the farthest to the +Y direction side out of the five left first portions **P1L**. Since a value obtained by multiplying the offset amount of the first portion **P1** in the X axis at the position of the left first portion **P1L** at the farthest to the +Y direction side by “-1” is 0.00 millimeter, the user inputs 0.00 millimeter as the X correction value. The position where the absolute value of the difference between the first distance **W1** and the second distance **W2** is the smallest in the Y axis is the position of the back first portion **P1B** at the second farthest to the -X direction side out of the five back first portions **P1B**. Since a value obtained by multiplying the offset amount of the first portion **P1** in the Y axis at the position of the back first portion **P1B** at the second farthest to the -X direction side by “-1” is -0.05 millimeter, the user inputs -0.05 millimeter as the Y correction value.

(85) In the step **S260**, the control section **300** determines whether or not the absolute value of the X correction value is lower than a predetermined value, and the absolute value of the Y correction value is lower than a predetermined value. In the present embodiment, the control section **300** determines whether or not the absolute value of the X correction value is lower than 0.05 millimeter (0.002 inch), and at the same time, the absolute value of the Y correction value is lower than 0.05 millimeter (0.002 inch).

(86) When it has not been determined in the step **S260** that the absolute value of the X correction value is lower than the predetermined value, and at the same time, the absolute value of the Y correction value is lower than the predetermined value, the control section **300** adjusts the relative position of the second nozzle **60B** with respect to the first nozzle **60A** in the X axis and the Y axis in accordance with the X correction value and the Y correction value in the step **S265**. In the present embodiment, the control section **300** controls the third drive section **213** to move the

second ejection section **100B** as much as the distance represented by the X correction value in parallel to the X axis to thereby adjust the relative position between the nozzles **60A**, **60B** in the X axis. The control section **300** controls the third drive section **213** to move the second ejection section **100B** as much as the distance represented by the Y correction value in parallel to the Y axis to thereby adjust the relative position between the nozzles **60A**, **60B** in the Y axis. For example, when the X correction value is 0.00 millimeter, and the Y correction value is -0.05 millimeter, the control section **300** moves the second ejection section **100B** as much as 0.05 millimeter toward the -Y direction in parallel to the Y axis without moving the second ejection section **100B** in parallel to the X axis. It should be noted that adjusting the relative position of the second nozzle **60B** to the first nozzle **60A** in accordance with the X correction value and the Y correction value is referred to as a third process, a third step of the calibration method of the three-dimensional modeling device **11**, or a third step of the calibration step in some cases.

(87) When adjusting the relative position between the nozzles **60A**, **60B** in the X axis and the Y axis in the step **S265**, the control section **300** returns the process to the step **S240** to shape the calibrating shaped articles **CM1**, **CM2** in accordance with the calibrating modeling data once again in order to confirm the adjustment condition of the relative position between the nozzles **60A**, **60B** in the X axis and the Y axis. The control section **300** repeats the processing in the step **S265** and the processing from the step **S240** to the step **S260** until it is determined in the step **S260** that the absolute value of the X correction value is lower than the predetermined value and at the same time the absolute value of the Y correction value is lower than the predetermined value. It should be noted that it is preferable for the calibrating shaped articles **CM1**, **CM2** shaped before the processing in the step **S265** to be removed by the user on the stage **220** in advance of the processing in the step **S265**.

(88) When it has been determined in the step **S260** that the absolute value of the X correction value is lower than the predetermined value, and at the same time the absolute value of the Y correction value is lower than the predetermined value, the control section **300** obtains a Z correction value in the step **S270**. In the present embodiment, the Z correction value is input by the user to the operation panel **120**. The control section **300** obtains the Z correction value input to the operation panel **120**. The user measures a thickness **t4** of the fourth portion **P4** of each of the calibrating shaped articles **CM1**, **CM2** using, for example, a vernier caliper, and then inputs the measurement value of the thickness **t4** of the fourth portion **P4** to the operation panel **120** as the Z correction value. In the present embodiment, the Z correction value can be input in terms of 0.01 millimeter (0.0005 inch).

(89) In the step **S280**, the control section **300** determines whether or not the absolute value of the Z correction value is lower than a predetermined value. In the present embodiment, the control section **300** determines whether or not the absolute value of the Z correction value is lower than 0.01 millimeter (0.0005 inch).

(90) When it has not been determined in the step **S280** that the absolute value of the Z correction value is lower than the predetermined value, the control section **300** adjusts the position of the second ejection section **100B** with respect to the stage **220** when ejecting the second material from the second nozzle **60B** in the step **S283** so that the distance between the stage **220** and the tip portion of the first nozzle **60A** when ejecting the first material from the first nozzle **60A** and the thickness **t4** of the fourth portion **P4** becomes equal to each other. In the present embodiment, the control section **300** moves the second ejection section **100B** along the Z axis using the third drive section **213** to thereby adjust the position of the second ejection section **100B** to the stage **220** when ejecting the second material from the second nozzle **60B**. It should be noted that in another embodiment, it is possible for the control section **300** to make the position of the stage **220** in the Z axis different using the first drive section **211** between when ejecting the first material from the first nozzle **60A** and when ejecting the second material from the second nozzle **60B** to thereby adjust the position of the second ejection section **100B** to the stage **220** when ejecting the second material

from the second nozzle **60B**.

(91) When it has been determined in the step **S280** that the absolute value of the Z correction value is lower than the predetermined value, the control section **300** stores execution history data of the calibration process in the memory in the step **S290**. The execution history data of the calibration process includes time and data when the calibration process has been executed, the type of the first material represented by the material data, the type of the second material represented by the material data, the X correction value, the Y correction value, and the Z correction value. When the processing in the step **S265** has been executed a plurality of times, the X correction value represented by the execution history data is represented as an accumulated value of the X correction values obtained a plurality of times in the step **S250**, and the Y correction value represented by the execution history data is represented as an accumulated value of the Y correction values obtained a plurality of times in the step **S250**. Subsequently, the control section **300** terminates this process.

(92) FIG. **13** is an explanatory diagram showing an operation history display screen SC to be displayed on the operation panel **120**. The operation history display screen SC is displayed on the operation panel **120** by the control section **300** when, for example, the user performs a predetermined operation to the operation panel **120**. In the operation history display screen SC, there are disposed fields of "OPERATION CONTENT," "TIME AND DATE," "MATERIAL," "X CORRECTION VALUE," "Y CORRECTION VALUE," and "Z CORRECTION VALUE" in this order from the left side. In the field of "OPERATION CONTENT," there is displayed the operation content having been performed on the three-dimensional modeling device **11** such as the calibration process, a nozzle replacement operation of replacing the nozzles **60A**, **60B**, a stage replacement operation of replacing the stage **220**, or a material replacement operation of replacing the material. In the field of "TIME AND DATE," there is displayed the time and the date when the operation has been performed. In the field of "MATERIAL," there is displayed the type of the material which has been housed in the material housing section **20** when the operation has been performed. When the material replacement operation has been performed, the type of the material after the replacement is displayed in the field of "MATERIAL." In the field of "X CORRECTION VALUE," the field of "Y CORRECTION VALUE," and the field of "Z CORRECTION VALUE," there are displayed the X correction value, the Y correction value, and the Z correction value represented by the execution history data in the calibration process. The control section **300** automatically obtains information which can automatically be obtained out of information to be displayed in the operation history display screen SC, and displays a screen for prompting the user to input information which cannot automatically be obtained on the operation panel **120**, and then obtain the information input by the user.

(93) In the operation history display screen SC, there can be displayed information related to a nozzle replacement operation, and information related to a stage replacement operation besides the information described above. For example, when the nozzle replacement operation has been executed, it is possible to display the types of the nozzles **60A**, **60B** after the replacement. When the stage replacement operation has been executed, it is possible to display the type of the stage **220** after the replacement.

(94) In the present embodiment, when the correction values represented in the execution history data of the latest calibration process are different as much as values no smaller than predetermined values from the correction values represented in the execution history data in the previous calibration process, the control section **300** displays a warning message on the operation panel **120**. It should be noted that in another embodiment, when the correction values represented in the execution history data of the latest calibration process are different as much as values no smaller than predetermined values from the average values of the correction values represented in the execution history data of the calibration processes executed within a predetermined period, the control section **300** can display a warning message on the operation panel **120**.

(95) According to the three-dimensional modeling device **11** of the present embodiment described hereinabove, the control section **300** shapes the calibrating shaped articles **CM1**, **CM2** in the calibration process. It is possible for the user to figure out the presence or absence of the displacement in the relative position between the nozzles **60A**, **60B** in the X axis and the Y axis, and the X correction value and the Y correction value for adjusting the relative position between the nozzles **60A**, **60B** using the calibrating shaped articles **CM1**, **CM2**. The control section **300** adjusts the relative position between the nozzles **60A**, **60B** in accordance with the X correction value and the Y correction value input by the user to reduce the displacement described above. Therefore, even when there occurs the displacement in the relative position between the nozzles **60A**, **60B**, by executing the calibration process in advance of the three-dimensional modeling process, it is possible to prevent the second nozzle **60B** from making contact with the modeling layer **ML** to deform the modeling layer **ML**, and the relative position of the support layer **SL** to the modeling layer **ML** from being displaced to deform the modeling layer **ML**. Therefore, it is possible to shape the three-dimensional shaped article **OB** with high dimensional accuracy.

(96) Further, in the present embodiment, the control section **300** shapes the calibrating shaped articles **CM1**, **CM2** in an area on the stage **220** designated by the user. Therefore, it is possible to shape the calibrating shaped articles **CM1**, **CM2** at the positions desired by the user. For example, it is possible to shape the calibrating shaped articles **CM1**, **CM2** at positions where the calibrating shaped articles **CM1**, **CM2** arranged on the stage **220** facilitate the operation of identifying the position where the first distance **W1** and the second distance **W2** are equal to each other, or positions where the calibrating shaped articles **CM1**, **CM2** are easily taken out from the modeling space **111**.

(97) Further, in the present embodiment, the control section **300** shapes the calibrating shaped articles **CM1**, **CM2** with which it is possible to figure out the X correction value and the Y correction value to be input to the operation panel **120** by identifying the position where the first distance **W1** and the second distance **W2** are equal to each other. Therefore, it is possible for the user to easily figure out the X correction value and the Y correction value which should be input to the operation panel **120**.

(98) Further, in the present embodiment, the control section **300** shapes the offset amount displaying shaped articles **DM1** representing the absolute values of the offset amounts of the first portions **P1** at the positions adjacent to the first portions **P1**, respectively. In the present embodiment, since the value obtained by multiplying the offset amount of the first portion **P1** by “-1” is the correction value, due to the offset amount displaying shaped articles **DM1**, it is possible to make it easy to make the user recognize the X correction value and the Y correction value which should be input to the operation panel **120**.

(99) Further, in the present embodiment, the control section **300** shapes the unit displaying shaped articles **DM2** representing the unit of the offset amount together with the calibrating shaped articles **CM1**, **CM2**, and can therefore prevent an inputting error of the correction values caused by a false recognition of the unit from occurring.

(100) Further, in the present embodiment, the control section **300** shapes the material displaying shaped article **DM3** representing the type of the first material and the type of the second material together with the calibrating shaped articles **CM1**, **CM2**, and can therefore make it easy to make the user recognize the type of the first material and the type of the second material.

(101) Further, in the present embodiment, the control section **300** shapes the calibrating shaped article **CM1** shaped using the low-temperature material and the calibrating shaped article **CM2** shaped using the high-temperature material so as to have respective shapes different from each other. Therefore, since it is possible to shape the calibrating shaped articles **CM1**, **CM2** having the shapes corresponding to the types of the materials, it is possible to prevent the deformation of the calibrating shaped articles **CM1**, **CM2** due to the shrinkage when the materials cool to shrink. In particular, in the present embodiment, the size of the calibrating shaped article **CM2** shaped in

accordance with the calibrating modeling data for the high-temperature material is larger than the size of the calibrating shaped article CM1 shaped in accordance with the calibrating modeling data for the low-temperature material. Therefore, the calibrating shaped article CM2 which is shaped using the high-temperature material large in shrinkage when the material cools to shrink compared to the low-temperature material can be prevented from deforming.

(102) Further, in the present embodiment, the control section 300 adjusts the position of the second nozzle 60B with respect to the stage 220 so that the distance between the stage 220 and the first nozzle 60A when ejecting the first material from the first nozzle 60A, and the thickness t4 of the fourth portion P4 becomes equal to each other. Therefore, it is possible to decrease the difference in thickness between the layer to be formed of the first material ejected from the first nozzle 60A and the layer to be formed of the second material ejected from the second nozzle 60B to thereby shape the three-dimensional shaped article with high dimensional accuracy.

(103) Further, in the present embodiment, the control section 300 stores the execution history data of the calibration process, and displays the information represented in the execution history data of the calibration process on the operation history display screen SC. Therefore, when an abnormality occurs in the three-dimensional modeling device 11, it is possible for the user to confirm whether or not the calibration process has been performed appropriately by referring to the operation history display screen SC, and therefore, it is possible to make it easy to take a countermeasure against the abnormality of the three-dimensional modeling device 11. In particular, in the present embodiment, when the correction values represented in the execution history data of the latest calibration process are different as much as values no smaller than predetermined values from the correction values represented in the execution history data in the previous calibration process, the control section 300 displays a warning message on the operation panel 120, and therefore, when an operating error occurs, it is possible to make it easy to become aware of the operating error.

B. Second Embodiment

(104) FIG. 14 is a top view showing a configuration of a calibrating shaped article CM3 to be shaped by a three-dimensional modeling process in a second embodiment. In a three-dimensional modeling device 12 according to the second embodiment, a shape of the calibrating shaped article CM3 to be shaped by the calibration process to be executed by the control section 300 is different from that in the first embodiment. The configuration of the three-dimensional modeling device 12, the content of the three-dimensional modeling process, and the content of the calibration process are the same as in the first embodiment unless particularly described.

(105) FIG. 14 shows the calibrating shaped article CM3 shaped in accordance with the calibrating modeling data for the low-temperature material. In the present embodiment, the left first portion P1L, the left second portion P2L, the right first portion P1R, and the right second portion P2R of the calibrating shaped article CM3 are each configured to be shaped like a single continuous straight line parallel to the Y axis. The front first portion P1F, the front second portion P2F, the back first portion P1B, and the back second portion P2B of the calibrating shaped article CM3 are each configured to be shaped like a single continuous straight line parallel to the X axis. The end portions of the first portions P1L, P1R, P1F, and P1B are coupled to each other, and the four first portions P1L, P1R, P1F, and P1B are formed to have a square frame-like shape. The end portions of the second portions P2L, P2R, P2F, and P2B are coupled to each other, and the four second portions P2L, P2R, P2F, and P2B are formed to have a square frame-like shape. Although the illustration is omitted, in the present embodiment, regarding the calibrating shaped article shaped in accordance with the calibrating modeling data for the high temperature, the left first portion P1L and the left second portion P2L are each configured to be shaped like a single continuous straight line parallel to the Y axis, and the front first portion P1F and the front second portion P2F are each configured to be shaped like a single continuous straight line parallel to the X axis.

(106) In the present embodiment, when no displacement occurs in the relative position between the nozzles 60A, 60B, the distance between the left first portion P1L and the left third portion P3L is

equal to the distance between the left second portion P2L and the left third portion P3L, and the distance between the front first portion P1F and the front third portion P3F is equal to the distance between the front second portion P2F and the front third portion P3F. When the displacement in the relative position in the X axis occurs between the nozzles 60A, 60B, the distance between the left first portion P1L and the left third portion P3L is different from the distance between the left second portion P2L and the left third portion P3L. When the displacement in the relative position in the Y axis occurs between the nozzles 60A, 60B, the distance between the front first portion P1F and the front third portion P3F is different from the distance between the front second portion P2F and the front third portion P3F.

(107) In the present embodiment, in the step S250 of the calibration process shown in FIG. 9, the control section 300 obtains the X correction value and the Y correction value input by the user to the operation panel 120 similarly to the first embodiment. The user measures the distance between the left first portion P1L and the left third portion P3L, and the distance between the left second portion P2L and the left third portion P3L to calculate a difference between the distance between the left first portion P1L and the left third portion P3L, and the distance between the left second portion P2L and the left third portion P3L. Further, the user measures the distance between the front first portion P1F and the front third portion P3F, and the distance between the front second portion P2F and the front third portion P3F to calculate a difference between the distance between the front first portion P1F and the front third portion P3F, and the distance between the front second portion P2F and the front third portion P3F. It is possible for the user to measure the distances described above using, for example, a vernier caliper. The user inputs a value obtained by dividing the difference between the distance between the left first portion P1L and the left third portion P3L, and the distance between the left second portion P2L and the left third portion P3L by “2” to the operation panel 120 as the X correction value, and inputs a value obtained by dividing the difference between the distance between the front first portion P1F and the front third portion P3F, and the distance between the front second portion P2F and the front third portion P3F by “2” to the operation panel 120 as the Y correction value.

(108) According to the three-dimensional modeling device 12 in the present embodiment described hereinabove, by the control section 300 executing the calibration process, it is possible to adjust the relative position between the nozzles 60A, 60B to thereby decrease the displacement in the relative position between the nozzles 60A, 60B similarly to the first embodiment.

C. Third Embodiment

(109) FIG. 15 is a front view showing a schematic configuration of a three-dimensional modeling device 13 according to a third embodiment. The third embodiment is different from the first embodiment in the point that the three-dimensional modeling device 13 is provided with a measurement section 500. The rest of the configuration, the content of the three-dimensional modeling process, and the content of the calibration process are the same as in the first embodiment unless particularly described.

(110) In the present embodiment, the measurement section 500 is fixed to the first ejection section 100A. The measurement section 500 measures the dimensions of the calibrating shaped articles CM1, CM2. The measurement section 500 is formed of a laser scanner, and scans the calibrating shaped articles CM1, CM2 with a laser beam to thereby measure the dimensions of the calibrating shaped articles CM1, CM2. The measurement section 500 is controlled by the control section 300. Information related to the dimensions of the calibrating shaped articles CM1, CM2 measured by the measurement section 500 is transmitted to the control section 300. In another embodiment, the measurement section 500 can be formed of a camera instead of the laser scanner. In this case, the control section 300 can obtain the X correction value, the Y correction value, and the Z correction value by analyzing an image taken by the camera. The measurement section 500 can be fixed to the second ejection section 100B instead of the first ejection section 100A, or can be disposed separately from the first ejection section 100A and the second ejection section 100B.

(111) In the present embodiment, the control section **300** obtains the X correction value and the Y correction value from the measurement section **500** in the step S250 in the calibration process shown in FIG. **9**. The measurement section **500** scans the calibrating shaped articles CM1, CM2 with the laser beam to thereby measure the first distance W1 and the second distance W2 in the portions of the calibrating shaped articles CM1, CM2, and then calculates the X correction value and the Y correction value.

(112) The control section **300** obtains the Z correction value from the measurement section **500** in the step S270 in the calibration process. The measurement section **500** scans the fourth portion P4 of the calibrating shaped articles CM1, CM2 with the laser beam to thereby measure the thickness t4 of the fourth portion P4, and then calculates the Z correction value. It should be noted that the measurement section **500** is referred to as a first measurement section or a second measurement section in some cases. Further, the measurement section for measuring the first distance W1 and the second distance W2, and the measurement section for measuring the thickness t4 of the fourth portion P4 can be disposed separately from each other. In this case, the measurement section for measuring the first distance W1 and the second distance W2 is referred to as a first measurement section, and the measurement section for measuring the thickness t4 of the fourth portion P4 is referred to as a second measurement section.

(113) According to the three-dimensional modeling device **13** in the present embodiment described hereinabove, by the control section **300** executing the calibration process, it is possible to adjust the relative position between the nozzles **60A**, **60B** to thereby decrease the displacement in the relative position between the nozzles **60A**, **60B** similarly to the first embodiment. In particular, in the present embodiment, since the correction values are calculated by the measurement section **500**, and the control section **300** obtains the correction values from the measurement section **500**, it is possible to save the effort of the user to calculate and then input the correction values, and at the same time, it is possible to eliminate a possibility that a false correction value is input due to a human error. It should be noted that in the three-dimensional modeling device **13** according to the present embodiment, it is possible for the control section **300** to shape the calibrating shaped article CM3 in the second embodiment.

(114) Further, in the present embodiment, since the control section **300** automatically repeats the shaping of the calibrating shaped articles CM1, CM2, the measurement of the calibrating shaped articles CM1, CM2 by the measurement section **500**, and the adjustment of the relative position between the nozzles **60A**, **60B**, it is possible to surely decrease the displacement in the relative position between the nozzles **60A**, **60B**.

D. Fourth Embodiment

(115) FIG. **16** is an explanatory diagram showing a schematic configuration of a three-dimensional modeling device **14** according to a fourth embodiment. In the three-dimensional modeling device **14** according to the fourth embodiment, a configuration of the first ejection section **101A** and a second ejection section **101B** is different from the configuration of the first ejection section **100A** and the second ejection section **100B** in the first embodiment. The rest of the configuration, the content of the three-dimensional modeling process, and the content of the calibration process are the same as in the first embodiment unless particularly described. Therefore, the configuration of the ejection sections **101A**, **101B** will mainly be described.

(116) The three-dimensional modeling device **14** according to the present embodiment is provided with the chassis **110**, the operation panel **120**, the first ejection section **101A**, the second ejection section **101B**, the drive section **210**, the stage **220**, and the control section **300**. The configuration of the second ejection section **101B** is the same as the configuration of the first ejection section **101A**. In the following description, when describing the first ejection section **101A** and the second ejection section **101B** without particularly discriminating the first ejection section **101A** and the second ejection section **101B** from each other, the first ejection section **101A** and the second ejection section **101B** are simply referred to as ejection sections **101**.

(117) In the present embodiment, in the modeling space **111** in the chassis **110**, there are housed the first ejection section **101A**, the second ejection section **101B**, and the stage **220**. The three-dimensional modeling device **14** is further provided with two blowers **16A**, **16B**. The blower **16A** is configured as a blower machine for feeding air toward the first ejection section **101A** via a manifold **17A**, and the blower **16B** is configured as a blower machine for feeding air toward the second ejection section **101B** via a manifold **17B**.

(118) In the present embodiment, a material housing section **21A** for housing the first material is arranged separately from the first ejection section **101A**, and a material housing section **21B** for housing the second material is arranged separately from the second ejection section **101B**. The material housing sections **21A**, **21B** are fixed to the chassis **110**. The material housing sections **21A**, **21B** are each configured as a holder for housing a material in the form of a filament. The material housing sections **21A**, **21B** are configured to be able to wind out the material housed inside to the outside of the material housing section **21A**, **21B**, respectively.

(119) FIG. **17** is an explanatory diagram showing a schematic configuration of the ejection section **101** in the present embodiment. The ejection section **101** is provided with a heating block **190** which has a heater, and functions as a plasticizing mechanism provided with an attachment hole **180**, a nozzle **160** detachably attached to the attachment hole **180**, and a material carrying mechanism **140** for carrying the material MF toward a nozzle channel **161** of the nozzle **160** attached to the heating block **190**. The ejection section **101** is further provided with a shield **168** which is disposed between the material carrying mechanism **140** in the Z axis and the heating block **190**, and suppresses the heat transfer from the heating block **190** to the material carrying mechanism **140**. In the present embodiment, the material carrying mechanism **140** is constituted by two wheels **149** without including the screw case **31** and the flat screw **41** unlike the first embodiment. The heating block **190** is not provided with the barrel **50** and the case section **91** unlike the first embodiment. The heating block **190** incorporates a heater not shown.

(120) The nozzle **160** in the present embodiment is inserted through the attachment hole **180** and a shield opening **169** provided to the shield **168** from the -Z direction to thereby be attached to the heating block **190**. In other words, in the present embodiment, the length of the nozzle **160** along the Z axis, and the length of the nozzle channel **161** along the Z axis are longer than the length of the attachment hole **180** along the Z axis. Therefore, in the present embodiment, the inflow port **165** provided to a rear end of the nozzle **160** is located at the +Z direction side with respect to the heating block **190**, more specifically, at the +Z direction side with respect to the shield **168**.

(121) The two wheels **149** constituting the material carrying mechanism **140** pull out the material MF in the material housing section **21** to the outside to guide the material MF between the two wheels **149**, and at the same time, carry the material MF toward the nozzle channel **161** of the nozzle **160** due to the rotation thereof. The heating block **190** plasticizes the material MF having been carried inside the nozzle channel **161** due to the heat of a heater not shown incorporated in the heating block **190**.

(122) The material MF in the present embodiment is cooled by the air fed from the blower **16** described above via the manifold **17** in the vicinity of the inflow port **165** of the nozzle **160**. Thus, the plasticization of the material MF in the vicinity of the inflow port **165** is suppressed, and the material MF is efficiently carried into the inflow port **165**. It should be noted that the output end **18** of the manifold **17** is located at the +Z direction side with respect to the shield **168**. Thus, since the air fed from the manifold **17** becomes easy to be guided to the vicinity of the inflow port **165** by the shield **168**, the material MF in the vicinity of the inflow port **165** is efficiently cooled.

(123) According to the three-dimensional modeling device **14** in the present embodiment described hereinabove, by the control section **300** executing the calibration process, it is possible to adjust the relative position between the nozzles **160A**, **160B** to thereby decrease the displacement in the relative position between the nozzles **160A**, **160B** similarly to the first embodiment. It should be noted that in the three-dimensional modeling device **14** according to the present embodiment, it is

possible for the control section **300** to execute the calibration process of the second embodiment. Further, it is possible for the three-dimensional modeling device **14** to be provided with the measurement section **500** similarly to the third embodiment, and it is possible for the control section **300** to execute the calibration process of the third embodiment.

E. Other Embodiments

(124) (E1) In the three-dimensional modeling devices **11** through **14** according to the embodiments described above, the control section **300** moves the second ejection section **100B**, **101B** to thereby adjust the relative position of the second nozzle **60B**, **160B** to the first nozzle **60A**, **160A** in the calibration process. In contrast, it is possible for the control section **300** to move the first ejection section **100A**, **101A** instead of the second ejection section **100B**, **101B** to thereby adjust the relative position of the second nozzle **60B**, **160B** to the first nozzle **60A**, **160A**, or to move both of the first ejection section **100A**, **101A** and the second ejection section **100B**, **101B** to thereby adjust the relative position of the second nozzle **60B**, **160B** to the first nozzle **60A**, **160A** in the calibration process. (E2) In the three-dimensional modeling devices **11** through **14** according to the embodiments described above, it is possible for the control section **300** to shape the shaped article representing at least one of the type of the first nozzle **60A**, **160A** mounted on the first ejection section **100A**, **101A** and the type of the second nozzle **60B**, **160B** mounted on the second ejection section **100B**, **101B** together with the calibrating shaped articles CM1 through CM3 in the calibration process. It is possible for the control section **300** to obtain the information related to the types of the nozzles **60A**, **60B**, **160A**, and **160B** input, for example, in advance by the user. In this case, it is possible to make it easy to make the user recognize the types of the nozzles **60A**, **60B**, **160A**, and **160B** mounted on the respective ejection sections **100A**, **100B**, **101A**, and **101B**. (E3) In the three-dimensional modeling devices **11** through **14** according to the embodiments described above, the length along the X axis and the length along the Y axis of the calibrating shaped article CM2 shaped by the control section **300** in accordance with the calibrating modeling data for the high-temperature material are longer than the length along the X axis and the length along the Y axis of the calibrating shaped article CM1 shaped by the control section **300** in accordance with the calibrating modeling data for the low-temperature material, respectively. In contrast, the length along the X axis and the length along the Y axis of the calibrating shaped article CM2 shaped by the control section **300** in accordance with the calibrating modeling data for the high-temperature material can be the same as the length along the X axis and the length along the Y axis of the calibrating shaped article CM1 shaped by the control section **300** in accordance with the calibrating modeling data for the low-temperature material, respectively. Further, the control section **300** is not required to make the calibrating modeling data different between when using the low-temperature material and when using the high-temperature material. In other words, it is possible to shape the calibrating shaped article the same in shape when using the low-temperature material and when using the high-temperature material. (E4) In the three-dimensional modeling devices **11**, **13**, and **14** according to the first embodiment, the third embodiment, and the fourth embodiment described above, the control section **300** shapes the calibrating shaped articles CM1, CM2 having the plurality of first portions P1 arranged with the offsets therebetween, the plurality of second portions P2 arranged with the offsets therebetween, and the third portion P3 arranged on a straight line between the first portions P1 and the second portions P2. In contrast, it is possible for the control section **300** to shape the calibrating shaped article having a plurality of first portions P1 arranged on a straight line, a plurality of second portions P2 arranged on a straight line, and a plurality of third portions P3 arranged between the first portions P1 and the second portions P2 with offsets therebetween. Further, in the offset amount displaying shaped articles DM1, it is possible to represent offset amounts of the third portions P3. Also in this case, it is possible for the user to figure out the correction values which should be input by figuring out the position where the distance between the first portion P1 and the third portion P3 and the distance between the second portion P2 and the third portion P3 are equal to each other. (E5) In the three-dimensional modeling

devices **11** through **14** according to the embodiments described above, the control section **300** adjusts the relative position of the second nozzle **60B**, **160B** to the first nozzle **60A**, **160A** in the Z axis in the calibration process. In contrast, the control section **300** is not required to adjust the relative position of the second nozzle **60B**, **160B** to the first nozzle **60A**, **160A** in the Z axis in the calibration process. (E6) In the three-dimensional modeling devices **11** through **14** according to the embodiments described above, the control section **300** stores the execution history data of the calibration process. In contrast, the control section **300** is not required to store the execution history data of the calibration process. In this case, it is possible to simplify the calibration process.

F. Other Aspects

(125) The present disclosure is not limited to the embodiments described above, but can be implemented in a variety of aspects within the scope or the spirit of the present disclosure. For example, the present disclosure can also be implemented in the following aspects. The technical features in the embodiments described above corresponding to the technical features in each of the aspects described below can arbitrarily be replaced or combined in order to solve some or all of the problems of the present disclosure, or to achieve some or all of the advantages of the present disclosure. Further, the technical feature can arbitrarily be eliminated unless described in the present specification as an essential element. (1) According to a first aspect of the present disclosure, there is provided a three-dimensional modeling device. The three-dimensional modeling device includes a first ejection section configured to eject a first material toward a stage, a second ejection section configured to eject a second material toward the stage, a drive section configured to move each of the first ejection section and the second ejection section relatively to the stage, and a control section configured to control the first ejection section, the second ejection section, and the drive section. The control section executes a calibration process including a first process of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second process of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third process of controlling the drive section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion to thereby adjust a relative position of the second ejection section to the first ejection section.

(126) The control section executes the first process and the second process once again when the third process is executed in the calibration process.

(127) According to the three-dimensional modeling device of this aspect, even when a displacement occurs in the relative position of the second ejection section to the first ejection section, it is possible to adjust the relative position of the second ejection section to the first ejection section due to the calibration process. Therefore, it is possible to shape the three-dimensional shaped article with high dimensional accuracy. (2) In the three-dimensional modeling device according to the aspect described above, in the calibration process, the control section may shape the calibrating shaped article in an area which is an area on the stage, and is designated by the user.

(128) According to the three-dimensional modeling device of this aspect, it is possible to shape the calibrating shaped article at the position desired by the user. (3) In the three-dimensional modeling device according to the aspect described above, the calibrating shaped article may have a plurality of the first portions and a plurality of the second portions arranged side by side along a first axis parallel to the first portion and the second portion, the control section may vary a position of the first ejection section in a second axis which is perpendicular to the first axis, and is parallel to the stage by the first portion and the second portion when shaping the plurality of the first portions and the plurality of the second portions, and the correction value may be a value corresponding to a variation in the position of the first ejection section in the second axis when a difference between a

distance between the first portion and the third portion and a distance between the second portion and the third portion is minimum.

(129) According to the three-dimensional modeling device of this aspect, it is possible to use the value corresponding to the variation in the position of the first ejection section as the correction value. (4) In the three-dimensional modeling device according to the aspect described above, the control section may shape a shaped article, which represents the variation in the position of the first ejection section when each of the first portions and the second portions is shaped, at a position corresponding to each of the first portions and the second portions in advance of the third process.

(130) According to the three-dimensional modeling device of this aspect, it is possible to make it easy to make the user recognize the variation in the position of the first ejection section. (5) In the three-dimensional modeling device according to the aspect described above, the calibrating shaped article may have a plurality of the third portions arranged side by side along a first axis parallel to the first portion and the second portion, the control section may vary a position of the second ejection section in a second axis which is perpendicular to the first axis, and is parallel to the stage by the third portion when shaping the plurality of the third portions, and the correction value may be a value corresponding to a variation in the position of the second ejection section in the second axis when a difference between a distance between the first portion and the third portion and a distance between the second portion and the third portion is minimum.

(131) According to the three-dimensional modeling device of this aspect, it is possible to use the value corresponding to the variation in the position of the second ejection section as the correction value. (6) In the three-dimensional modeling device according to the aspect described above, the control section may shape a shaped article, which represents the variation in the position of the second ejection section when each of the third portions is shaped, at a position corresponding to each of the third portions in advance of the third process.

(132) According to the three-dimensional modeling device of this aspect, it is possible to make it easy to make the user recognize the variation in the position of the second ejection section. (7) In the three-dimensional modeling device according to the aspect described above, the control section may shape a shaped article representing a unit of the correction value in advance of the third process.

(133) According to the three-dimensional modeling device of this aspect, it is possible to suppress the false recognition of the unit of the correction value by the user. (8) In the three-dimensional modeling device according to the aspect described above, the control section may shape a shaped article representing at least one of a type of the first material and a type of the second material in advance of the third process.

(134) According to the three-dimensional modeling device of this aspect, it is possible to make it easy to make the user recognize the type of the material. (9) In the three-dimensional modeling device according to the aspect described above, the control section may make a shape of the calibrating shaped article different by a type of the first material or a type of the second material.

(135) According to the three-dimensional modeling device of this aspect, by adopting a shape corresponding to the type of the material as the shape of the calibrating shaped article, it is possible to prevent the calibrating shaped article from deforming when the material cools to shrink. (10) In the three-dimensional modeling device according to the aspect described above, when at least one of a melting temperature of the first material and a melting temperature of the second material exceeds a predetermined temperature, the control section may shape the calibrating shaped article having a larger shape compared to when at least one of the melting temperature of the first material and the melting temperature of the second material is no higher than the temperature.

(136) According to the three-dimensional modeling device of this aspect, it is possible to prevent the calibrating shaped article from deforming when the material cools to shrink. (11) In the three-dimensional modeling device according to the aspect described above, the control section may shape a shaped article representing at least one of a type of a first nozzle which is mounted on the

first ejection section, and is configured to eject the first material, and a type of a second nozzle which is mounted on the second ejection section, and is configured to eject the second material in advance of the third process.

(137) According to the three-dimensional modeling device of this aspect, it is possible to make it easy to make the user recognize the type of the nozzle. (12) In the three-dimensional modeling device according to the aspect described above, the control section may store an execution history representing that the calibration process was executed.

(138) According to the three-dimensional modeling device of this aspect, when an abnormality occurs in the three-dimensional modeling device, it is possible to check the execution history of the calibration process. (13) In the three-dimensional modeling device according to the aspect described above, there may further be included a first measurement section configured to obtain relative positions of the third portion to the first portion and the second portion, wherein the control section may obtain the correction value from the first measurement section.

(139) According to the three-dimensional modeling device of this aspect, since the control section automatically obtains the correction value from the first measurement section, it is possible to reduce the burden on the user compared to the aspect in which the control section obtains the correction value input by the user. (14) In the three-dimensional modeling device according to the aspect described above, the control section may repeat the shaping of the calibrating shaped article and the acquisition of the correction value from the first measurement section until the correction value becomes no higher than a predetermined value in the calibration process.

(140) According to the three-dimensional modeling device of this aspect, since the control section automatically repeats the shaping of the calibrating shaped article and the measurement by the first measurement section, it is possible to reduce the burden on the user. (15) In the three-dimensional modeling device according to the aspect described above, there may further be included a second measurement section configured to measure a thickness of the calibrating shaped article, wherein the calibrating shaped article may have a fourth portion which is shaped with the second material ejected from the second ejection section, and the control section may measure a thickness of the fourth portion with the second measurement section to adjust the position of the second ejection section to the stage so that a distance between the stage and the first ejection section when ejecting the first material and the thickness of the fourth portion become equal to each other after the correction value becomes no higher than a predetermined value in the calibration process.

(141) According to the three-dimensional modeling device of this aspect, since it is possible to decrease the difference in thickness between the layer to be formed of the first material ejected from the first ejection section and the layer to be formed of the second material ejected from the second ejection section, it is possible to shape the three-dimensional shaped article with high dimensional accuracy. (16) According to a second aspect of the present disclosure, there is provided a method of calibrating a three-dimensional modeling device provided with a first ejection section configured to eject a first material toward a stage, and a second ejection section configured to eject a second material toward the stage. The method of calibrating the three-dimensional modeling device includes a first step of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second step of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third step of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion. When the third step is executed, the first step and the second step are executed once again.

(142) According to the method of calibrating the three-dimensional modeling device of this aspect, even when a displacement occurs in the relative position of the second ejection section to the first

ejection section, it is possible to adjust the relative position of the second ejection section to the first ejection section. Therefore, it is possible to shape the three-dimensional shaped article with high dimensional accuracy. (17) According to a third aspect of the present disclosure, there is provided a method of manufacturing a three-dimensional shaped article. The method of manufacturing a three-dimensional shaped article includes a shaping step of shaping the three-dimensional shaped article using a first ejection section configured to eject a first material toward a stage, and a second ejection section configured to eject a second material toward the stage, and a calibration step of adjusting a relative position of the second ejection section to the first ejection section in advance of the shaping step. The calibration step includes a first step of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second step of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third step of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion. In the calibration step, when the third step is executed, the first step and the second step are executed once again.

(143) According to the method of manufacturing the three-dimensional shaped article of this aspect, even when a displacement occurs in the relative position of the second ejection section to the first ejection section, it is possible to adjust the relative position of the second ejection section to the first ejection section due to the calibration step. Therefore, it is possible to shape the three-dimensional shaped article with high dimensional accuracy in the shaping step.

(144) The present disclosure can be implemented in a variety of aspects other than the three-dimensional modeling device. For example, the present disclosure can also be implemented as an aspect such as a method of calibrating a three-dimensional modeling device, or a method of manufacturing a three-dimensional shaped article.

Claims

1. A three-dimensional modeling device comprising: a first ejection section configured to eject a first material toward a stage; a second ejection section configured to eject a second material toward the stage; a drive section configured to move each of the first ejection section and the second ejection section relatively to the stage; and a control section configured to control the first ejection section, the second ejection section, and the drive section, wherein the control section executes a calibration process including a first process of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second process of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third process of controlling the drive section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion to thereby adjust a relative position of the second ejection section to the first ejection section, the control section executes the first process and the second process once again when the third process is executed in the calibration process, the calibrating shaped article has a fourth portion which is shaped with the second material ejected from the second ejection section, the second portion is arranged between the third and fourth portions, a first measurement section is configured to obtain relative positions of the third portion to the first portion and the second portion, the control section obtains the correction value from the first measurement section, the control section repeats the shaping of the calibrating shaped article and

the acquisition of the correction value from the first measurement section until the correction value becomes no higher than a predetermined value in the calibration process, a second measurement section is configured to measure a thickness of the calibrating shaped article, and the control section measures a thickness of the fourth portion with the second measurement section to adjust the position of the second ejection section to the stage so that a distance between the stage and the first ejection section when ejecting the first material and the thickness of the fourth portion become equal to each other after the correction value becomes no higher than a predetermined value in the calibration process.

2. The three-dimensional modeling device according to claim 1, wherein in the calibration process, the control section shapes the calibrating shaped article in an area which is an area on the stage, and is designated by the user.

3. The three-dimensional modeling device according to claim 1, wherein the calibrating shaped article has a plurality of the first portions and a plurality of the second portions arranged side by side along a first axis parallel to the first portion and the second portion, the control section varies a position of the first ejection section in a second axis which is perpendicular to the first axis, and is parallel to the stage by the first portion and the second portion when shaping the plurality of the first portions and the plurality of the second portions, and the correction value is a value corresponding to a variation in the position of the first ejection section in the second axis when a difference between a distance between the first portion and the third portion and a distance between the second portion and the third portion is minimum.

4. The three-dimensional modeling device according to claim 3, wherein the control section shapes a shaped article, which represents the variation in the position of the first ejection section when each of the first portions and the second portions is shaped, at a position corresponding to each of the first portions and the second portions in advance of the third process.

5. The three-dimensional modeling device according to claim 1, wherein the calibrating shaped article has a plurality of the third portions arranged side by side along a first axis parallel to the first portion and the second portion, the control section varies a position of the second ejection section in a second axis which is perpendicular to the first axis, and is parallel to the stage by the third portion when shaping the plurality of the third portions, and the correction value is a value corresponding to a variation in the position of the second ejection section in the second axis when a difference between a distance between the first portion and the third portion and a distance between the second portion and the third portion is minimum.

6. The three-dimensional modeling device according to claim 5, wherein the control section shapes a shaped article, which represents the variation in the position of the second ejection section when each of the third portions is shaped, at a position corresponding to each of the third portions in advance of the third process.

7. The three-dimensional modeling device according to claim 1, wherein the control section shapes a shaped article representing a unit of the correction value in advance of the third process.

8. The three-dimensional modeling device according to claim 1, wherein the control section shapes a shaped article representing at least one of a type of the first material and a type of the second material in advance of the third process.

9. The three-dimensional modeling device according to claim 1, wherein the control section makes a shape of the calibrating shaped article different by a type of the first material or a type of the second material.

10. The three-dimensional modeling device according to claim 1, wherein when at least one of a melting temperature of the first material and a melting temperature of the second material exceeds a predetermined temperature, the control section shapes the calibrating shaped article having a larger shape compared to when at least one of the melting temperature of the first material and the melting temperature of the second material is no higher than the predetermined temperature.

11. The three-dimensional modeling device according to claim 1, wherein the control section

shapes a shaped article representing at least one of a type of a first nozzle which is mounted on the first ejection section, and is configured to eject the first material, and a type of a second nozzle which is mounted on the second ejection section, and is configured to eject the second material in advance of the third process.

12. The three-dimensional modeling device according to claim 1, wherein the control section stores an execution history representing that the calibration process was executed.

13. The three-dimensional modeling device according to claim 1, wherein the second portion is arranged between the third and fourth portions, a first distance between the first portion and the third portion and a second distance between the second portion and the third portion are equal to each other, and a third distance between the second portion and the fourth portion is greater than the first and second distances.

14. A method of calibrating a three-dimensional modeling device provided with a first ejection section configured to eject a first material toward a stage, and a second ejection section configured to eject a second material toward the stage, the method comprising: a first step of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage; a second step of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article; and a third step of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion, wherein when the third step is executed, the first step and the second step are executed once again, the calibrating shaped article has a fourth portion which is shaped with the second material ejected from the second ejection section, the second portion is arranged between the third and fourth portions, a first measurement section is configured to obtain relative positions of the third portion to the first portion and the second portion, the control section obtains the correction value from the first measurement section, the control section repeats the shaping of the calibrating shaped article and the acquisition of the correction value from the first measurement section until the correction value becomes no higher than a predetermined value in the calibration process, a second measurement section is configured to measure a thickness of the calibrating shaped article, and the control section measures a thickness of the fourth portion with the second measurement section to adjust the position of the second ejection section to the stage so that a distance between the stage and the first ejection section when ejecting the first material and the thickness of the fourth portion become equal to each other after the correction value becomes no higher than a predetermined value in the calibration process.

15. A method of manufacturing a three-dimensional shaped article, comprising: a shaping step of shaping the three-dimensional shaped article using a first ejection section configured to eject a first material toward a stage, and a second ejection section configured to eject a second material toward the stage; and a calibration step of adjusting a relative position of the second ejection section to the first ejection section in advance of the shaping step, wherein the calibration step includes a first step of ejecting the first material from the first ejection section to thereby shape a first portion and a second portion shaped like straight lines arranged in parallel to the stage and in parallel to each other in a calibrating shaped article to be shaped on the stage, a second step of ejecting the second material from the second ejection section to thereby shape a third portion shaped like a straight line arranged between the first portion and the second portion in the calibrating shaped article, and a third step of adjusting a relative position of the second ejection section to the first ejection section in accordance with a correction value obtained based on relative positions of the third portion to the first portion and the second portion, wherein in the calibration step, when the third step is executed, the first step and the second step are executed once again, the calibrating shaped article has a fourth portion which is shaped with the second material ejected from the second ejection section, the

second portion is arranged between the third and fourth portions, a first measurement section is configured to obtain relative positions of the third portion to the first portion and the second portion, the control section obtains the correction value from the first measurement section, the control section repeats the shaping of the calibrating shaped article and the acquisition of the correction value from the first measurement section until the correction value becomes no higher than a predetermined value in the calibration process, a second measurement section is configured to measure a thickness of the calibrating shaped article, and the control section measures a thickness of the fourth portion with the second measurement section to adjust the position of the second ejection section to the stage so that a distance between the stage and the first ejection section when ejecting the first material and the thickness of the fourth portion become equal to each other after the correction value becomes no higher than a predetermined value in the calibration process.
