

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250277306

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

NISHIKAWA; Naohiro et al.

DIAMOND FILM-DEPOSITED SUBSTRATE AND METHOD FOR MANUFACTURING DIAMOND FILM-DEPOSITED SUBSTRATE

Abstract

There is provided a diamond film-deposited substrate, including: a substrate comprising niobium metal; a niobium carbide layer on at least one main surface of the substrate; and a conductive diamond film on the niobium carbide layer, wherein when a surface of the conductive diamond film was observed using a scanning electron microscope, no pinholes reaching the substrate or the niobium carbide layer are present within a field of view of 20 μm ×20 μm .

Inventors:	NISHIKAWA; Naohiro (Hitachi-shi, JP), MORITA; Toshiaki (Hitachi-shi, JP), KURIHARA; Kaori (Hitachi-shi, JP)
Applicant:	SUMITOMO CHEMICAL COMPANY, LIMITED (Tokyo, JP)
Family ID:	88518538
Assignee:	SUMITOMO CHEMICAL COMPANY, LIMITED (Tokyo, JP)
Appl. No.:	18/859148
Filed (or PCT Filed):	March 06, 2023
PCT No.:	PCT/JP2023/008214

Foreign Application Priority Data

JP	2022-072370	Apr. 26, 2022
----	-------------	---------------

Publication Classification

Int. Cl.: C23C16/27 (20060101); C23C8/64 (20060101); C23C28/00 (20060101); C30B28/14 (20060101); C30B29/04 (20060101)

U.S. Cl.:

CPC C23C16/271 (20130101); C23C8/64 (20130101); C23C28/341 (20130101); C30B28/14 (20130101); C30B29/04 (20130101);

Background/Summary

TECHNICAL FIELD

[0001] The present invention relates to a diamond film-deposited substrate and a method for manufacturing a diamond film-deposited substrate.

DESCRIPTION OF RELATED ART

[0002] Conductive diamond has a wide potential window in both aqueous and non-aqueous systems, with small background current, thus making it known as an electrode material capable of performing highly sensitive electrochemical detection over a wide potential range.

[0003] For example, Patent document 1 discloses a method for manufacturing a conductive diamond electrode, including: applying plastic treatment to at least a surface of an electrode substrate comprising a material such as valve metals selected from the group consisting of niobium, tantalum, titanium and zirconium, and alloys based on these metals; next, applying heat treatment to the electrode substrate in a vacuum or in an inert atmosphere; and forming a conductive diamond film on a surface of the heat-treated electrode substrate.

PRIOR ART DOCUMENT

Patent Document

[0004] [Patent Document 1] Patent publication No. 4456378

SUMMARY OF THE INVENTION

Problem to be Solved by the Invention

[0005] An object of the present invention is to provide a diamond film-deposited substrate capable of improving the durability of a diamond electrode.

Means for Solving the Problem

[0006] According to an aspect of the present invention, there is provided a diamond film-deposited substrate, including: [0007] a substrate comprising niobium metal; [0008] a niobium carbide layer on at least one main surface of the substrate; and [0009] a conductive diamond film on the niobium carbide layer, [0010] wherein when a surface of the conductive diamond film is observed using a scanning electron microscope, no pinholes reaching the substrate or the niobium carbide layer are present within a field of view of 20 μm ×20 μm .

[0011] According to another aspect of the present invention, there is provided a method for manufacturing a diamond film-deposited substrate, the method including: [0012] forming a processing damage layer having microcracks by introducing processing damage onto at least one main surface of a substrate comprising niobium metal; [0013] embedding a carbon source comprising a solid carbon or carbon compound into the processing damage layer; [0014] applying a heat treatment to the processing damage layer to cause a reaction between the niobium metal and the carbon source to form a niobium carbide layer continuously covering the main surface; and [0015] depositing a conductive diamond film on the niobium carbide layer.

Advantage of the Invention

[0016] According to the present invention, it is possible to provide a diamond film-deposited substrate capable of improving the durability of a diamond electrode.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] FIG. 1 is a schematic view illustrating a cross section of a diamond film-deposited substrate **10** according to a first embodiment of the present invention.

[0018] FIG. 2 is a flow chart showing an example of a method for manufacturing the diamond film-deposited substrate **10** according to the first embodiment of the present invention.

[0019] FIG. 3(a) is a schematic view illustrating a processing damage layer forming step **S102** according to the first embodiment of the present invention, and FIG. 3(b) is a schematic view illustrating a carbon source embedding step **S103** according to the first embodiment of the present invention.

[0020] FIG. 4 is a schematic view illustrating a cross section of the diamond film-deposited substrate **10** according to a modified example of the first embodiment of the present invention.

[0021] FIG. 5(a) is a surface photograph of Sample 1 according to an example of the present invention, FIG. 5(b) is a surface photograph of Sample 2 according to an example of the present invention, FIG. 5(c) is a surface photograph of Sample 3 according to an example of the present invention, and FIG. 5(d) is a surface photograph of Sample 4 according to an example of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

<Finding Obtained by the Present Inventors>

[0022] First, the finding obtained by the present inventors will be described.

[0023] A diamond electrode that has been made conductive by doping it with boron, etc., can be used to generate oxidizing agents such as ozone. Durability is a major issue for such a diamond electrode. Although the technique described in Patent document 1, etc., has improved the adhesion and peel strength between a substrate and a diamond film, it has been found that it is difficult to obtain a practical level of durability.

[0024] For example, paragraph 0009 of Patent document 1 states that “when an intermediate layer is made of carbide derived from a substrate, it is expected that the adhesion of a diamond film will be improved due to a relationship between the substrate and the carbide growing from the substrate, and a relationship between a carbide and a diamond generated with the carbide as a nucleus.

However, in reality, carbides often have inferior corrosion resistance to oxides when a potential is applied to them as an anode in a strong acidic environment. Carbide is likely to be formed on the substrate when it comes into contact with hydrocarbon radicals or diamond at a high temperature, so care must be taken when using it as an anode.” From the viewpoint of improving durability, it has been considered preferable to prevent as much carbide as possible from being formed on the intermediate layer between the substrate and the diamond film.

[0025] The present inventors have conducted extensive research into the above-described carbide layer. As a result, it was found that the carbide layer only inhibits the durability of the diamond electrode when it comes into contact with a strongly acidic liquid, and that the essence of the problem is the presence of pinholes on the surface of the diamond film that reach the substrate or the carbide layer. It was also found that an occurrence of the pinholes can be suppressed by intentionally forming a continuous carbide layer as an intermediate layer. In order to form the continuous carbide layer, for example, it has been found to be effective to introduce processing damage into a substrate to form a processing damage layer having microcracks, embed a carbon source in the processing damage layer, and then apply a heat treatment thereto.

DETAILS OF THE EMBODIMENT OF THE PRESENT INVENTION

[0026] Next, an embodiment of the present invention will be described below with reference to the drawings. The present invention is not limited to these embodiments, but is defined by the claims, and is intended to include all modifications within the meaning and scope of the claims.

First Embodiment of the Present Invention

(1) Configuration of a Diamond Film-Deposited Substrate **10**

[0027] First, the configuration of the diamond film-deposited substrate **10** of this embodiment will be described. The diamond film-deposited substrate **10** of this embodiment is preferably used for manufacturing a diamond electrode for an electrochemical reaction (for example, for ozone generation). This makes it possible to suppress deterioration of the diamond electrode due to electrical conduction and improve its durability.

[0028] FIG. **1** is a schematic view illustrating the cross section of the diamond film-deposited substrate **10** according to this embodiment. As illustrated in FIG. **1**, the diamond film-deposited substrate **10** includes, for example, a substrate **20**, a niobium carbide layer **30**, and a conductive diamond film **40**.

[0029] The substrate **20** is, for example, a flat niobium metal plate material for depositing the conductive diamond film **40** and for supporting the conductive diamond film **40**. The size and thickness of the main surface of the substrate **20** are not particularly limited, but for example, the main surface has a rectangular shape with one side measuring 20 mm to 500 mm, and a thickness measuring 0.5 mm to 5 mm.

[0030] The niobium carbide layer **30** is formed, for example, on at least one main surface of the substrate **20**, and is a layer formed by a reaction between a part of the niobium metal of the substrate **20** and a carbon source **22** described below. The niobium carbide layer **30** functions, for example, as an intermediate layer to increase a nucleation density of diamond crystals.

[0031] The thickness of the niobium carbide layer **30** is preferably, for example, 0.5 μm or more and 5 μm or less (more preferably 0.8 μm or more and 2.5 μm or less). That is, a maximum thickness and a minimum thickness of the niobium carbide layer **30** are preferably within a range of 0.5 μm or more and 5 μm or less (more preferably, 0.8 μm or more and 2.5 μm or less). When the thickness of the niobium carbide layer **30** is less than 0.5 μm , the nucleation density of the diamond crystals for forming the conductive diamond film **40** may be insufficient. Meanwhile, by setting the thickness of the niobium carbide layer **30** to 0.5 μm or more, the nucleation density of the diamond crystals for forming the conductive diamond film **40** can be sufficiently increased. On the other hand, when the thickness of the niobium carbide layer **30** exceeds 5 μm , an internal stress increases, and there is a possibility that the diamond film-deposited substrate **10** will be warped. Meanwhile, by setting the thickness of the niobium carbide layer **30** to 5 μm or less, the internal stress can be reduced, and warping of the diamond film-deposited substrate **10** can be reduced.

[0032] The conductive diamond film **40** is, for example, a polycrystalline film having electrical conductivity that is formed on the niobium carbide layer **30**. The conductive diamond film **40** may be either a polycrystalline diamond film or a diamond-like carbon (DLC) film. The conductive diamond film **40** preferably contains, for example, boron at a concentration of 1×10^{19} cm⁻³ or more and 1×10^{22} cm⁻³ or less. The thickness of the conductive diamond film **40** is, for example, 0.5 μm or more and 10 μm or less, and from the viewpoint of maintaining a balance between durability and cost, it is preferably 1 μm or more and 5 μm or less. This embodiment shows a case in which the conductive diamond film **40** has a single layer structure.

[0033] When the surface of the conductive diamond film **40** is observed using, for example, a scanning electron microscope (for example, 5000 times magnification), no pinholes reaching the substrate **20** or the niobium carbide layer **30** are present within a 20 $\mu\text{m} \times 20 \mu\text{m}$ field of view. Therefore, it is possible to reduce the risk of the strongly acidic liquid coming into contact with the niobium carbide layer **30** even when the diamond electrode is used in a strongly acidic liquid, for example, and possible to improve the durability of the diamond electrode. From the viewpoint of further improving the durability of the diamond electrode, it is preferable that no pinholes reaching the substrate **20** or the niobium carbide layer **30** are present within a field of view of 1 mm $\times$ 1 mm, and it is particularly preferable that no pinholes are present over an entire surface of the conductive diamond film **40**.

[0034] Further, when the cross section (longitudinal or transverse section) of the conductive diamond film **40** is observed using, for example, a scanning electron microscope (for example,

5000 times magnification), it is preferable that no pinholes reaching the substrate **20** or the niobium carbide layer **30** are present within a $20\ \mu\text{m} \times 20\ \mu\text{m}$ field of view. That is, in the conductive diamond film **40**, not only pinholes observable from the surface but also internal pinholes are reduced. Thereby, the durability of the diamond electrode can be further improved. It is more preferable that no pinholes reaching the substrate **20** or the niobium carbide layer **30** are present within a field of view of $1\ \text{mm} \times 1\ \text{mm}$ in the cross section (longitudinal or transverse section) of the conductive diamond film **40**, and it is particularly preferable that no pinholes are present over an entire cross section of the conductive diamond film **40**.

[0035] When the cross section of the diamond film-deposited substrate **10** is observed using, for example, a scanning electron microscope (for example, 5000 times magnification), it is preferable that a continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is formed over a width (length in a direction parallel to the main surface of the substrate **20**) of $20\ \mu\text{m}$ or more. Thereby, the nucleation density of the diamond crystals for forming the conductive diamond film **40** can be increased and the occurrence of pinholes can be suppressed. From the viewpoint of further suppressing the occurrence of pinholes, it is more preferable that a continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is formed over a width of $1\ \text{mm}$ or more, and it is particularly preferable that a continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is formed over an entire main surface of the substrate **20**.

[0036] The main component of the niobium carbide layer **30** is preferably niobium carbide, for example, having a chemical formula NbC. Thereby, the nucleation density of the diamond crystals for forming the conductive diamond film **40** can be increased. The main component of the niobium carbide layer **30** can be confirmed by, for example, X-ray diffraction (XRD).

[0037] The crystallite size of the niobium carbide contained in the niobium carbide layer **30** is preferably, for example, $1\ \text{nm}$ or more and $60\ \text{nm}$ or less. When the crystallite size is outside the above range, it may be difficult to form the continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more. In contrast, with the crystallite size within the above range, the continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is easily formed, and as a result, the occurrence of pinholes is easily suppressed. In this specification, each crystallite size can be measured, for example, by the Scherrer method of XRD. When the diamond film-deposited substrate **10** is measured by XRD, peaks of NbC (111), NbC (200), NbC (222), NbC (400), etc., are observed, with the NbC (111) peak being the strongest. Therefore, in this specification, unless otherwise specified, the crystallite size of niobium carbide was calculated from the peak of NbC (111).

[0038] The crystallite size of the niobium metal contained in the substrate **20** (particularly the niobium metal present in the vicinity of an interface with the niobium carbide layer **30**) is preferably, for example, $30\ \text{nm}$ or more and $90\ \text{nm}$ or less. When the crystallite size of the niobium metal is less than $30\ \text{nm}$, it may be difficult to form the continuous niobium carbide layer **30**. Meanwhile, by setting the crystallite size of the niobium metal to $30\ \text{nm}$ or more, the continuous niobium carbide layer **30** is easily formed. On the other hand, when the crystallite size of the niobium metal exceeds $90\ \text{nm}$, the difference in crystallite size with respect to the niobium carbide contained in the niobium carbide layer **30** becomes large, and cracks, etc., may occur. Meanwhile, by setting the crystallite size of the niobium metal to $90\ \text{nm}$ or less, the crystallite size is distributed so as to gradually decrease from the substrate **20** to the niobium carbide layer **30**, so the occurrence of cracks, etc., can be suppressed. When the diamond film-deposited substrate **10** is measured by XRD (from the conductive diamond film **40** side), peaks such as Nb (110), Nb (200), and Nb (211) are observed, with the Nb (110) peak being the strongest. Therefore, in this specification, unless otherwise specified, the crystallite size of the niobium metal was calculated from the peak of Nb (110).

(2) Method for Manufacturing a Diamond Film-Deposited Substrate **10**

[0039] Next, a method for manufacturing the diamond film-deposited substrate **10** of this

embodiment will be described. As described above, the diamond film-deposited substrate **10** of this embodiment can be used to manufacture a diamond electrode for an electrochemical reaction (e.g., for ozone generation). Therefore, the present invention is also applicable as a method for manufacturing a diamond electrode.

[0040] FIG. **2** is a flow chart showing an example of the method for manufacturing a diamond film-deposited substrate **10** of this embodiment. As shown in FIG. **2**, the method for manufacturing a diamond film-deposited substrate **10** of this embodiment includes, for example, an unevenness forming step **S101**, a processing damage layer forming step **S102**, a carbon source embedding step **S103**, a seeding step **S104**, a niobium carbide layer forming step **S105**, and a diamond film depositing step **S106**. This embodiment shows a case in which the diamond film-deposited substrate **10** is manufactured from the substrate **20** comprising niobium metal.

(Unevenness Forming Step **S101**)

[0041] The unevenness forming step **S101** is, for example, a step of performing processing to form unevenness on at least one main surface of the substrate **20**. Thereby, peeling caused by a difference in thermal expansion coefficient between the substrate **20** and the conductive diamond film **40**, can be suppressed. That is, a peel strength of the diamond film-deposited substrate **10** can be further improved. In the unevenness forming step **S101**, it is preferable to form the unevenness so that the arithmetic mean roughness Ra (see JIS B0601-2001) of the main surface is 0.5 μm or more and 10 μm or less. The processing for forming the unevenness can be performed by a known method such as grinding, blasting, wet etching, and dry etching.

[0042] The unevenness forming step **S101** is preferably performed, for example, before the processing damage layer forming step **S102**. When the processing for forming unevenness is performed to the surface on which the processing damage layer **21** is formed, there is a possibility that the processing damage layer **21** will be removed.

[0043] Meanwhile, by performing the unevenness forming step **S101** before the processing damage layer forming step **S102**, work-hardening occurs in the substrate **20**, and therefore microcracks are likely to be formed in the processing damage layer forming step **S102**. Further, in the unevenness forming step **S101**, in order to further work-harden the substrate **20**, further machining such as punching or grooving may be performed.

[0044] The unevenness forming step **S101** may be omitted. In the method for manufacturing the diamond film-deposited substrate **10** according to this embodiment, even when the unevenness forming step **S101** is omitted, by performing the processing damage layer forming step **S102** and the carbon source embedding step **S103** described later, the niobium carbide layer **30** that continuously covers the main surface of the substrate **20** can be formed in the niobium carbide layer forming step **S105**. That is, the occurrence of pinholes on the conductive diamond film **40** can be suppressed.

(Processing Damage Layer Forming Step **S102**)

[0045] FIG. **3(a)** is a schematic view illustrating the processing damage layer forming step **S102**. As illustrated in FIG. **3(a)**, the processing damage layer forming step **S102** is a step of forming a processing damage layer **21** having a large number of microcracks by introducing processing damage onto at least one main surfaces of the substrate **20** (the surface on which unevenness is formed at least in the unevenness forming step **S101**). In order to dissolve carbon in niobium metal and form niobium carbide, heating to over 2300 degrees is usually required, but by forming the processing damage layer **21**, the diffusion of carbon atoms into the niobium metal is promoted even at a low temperature (for example, about 800 degrees), and the niobium carbide layer **30** becomes easier to be formed. The method for introducing processing damage is not particularly limited as long as it is a method capable of forming microcracks. Specifically, processing damage can be introduced by grinding, imprinting, blasting, pressing, etc., to form the processing damage layer **21** having microcracks. In this specification, the microcracks include not only cracks having a length of 0.1 μm or more and 2 μm or less and a width of 5 nm or more and 200 nm or less (hereinafter,

this will also be referred to as microcracks with voids), but also grain boundaries where crystal defects are gathered and arranged at a high density (hereinafter, this will also be referred to as microcracks without voids). That is, the microcracks as used herein do not necessarily involve voids. Microcracks can be confirmed, for example, by observing the main surface of the substrate **20** with a scanning electron microscope. Further, in the processing damage layer forming step **S102**, for example, it is preferable to form microcracks having a depth of 0.5 μm or more and 5 μm or less at a density of $10.\text{sup.}8/\text{cm}.\text{sup.}2$ or more and $10.\text{sup.}9/\text{cm}.\text{sup.}2$ or less. Thereby, the carbon source **22** can be more easily embedded inside the microcracks in the carbon source embedding step **S103** described later.

[0046] In the processing damage layer forming step **S102**, for example, it is preferable to form the processing damage layer **21** with a thickness of 0.5 μm or more and 5 μm or less (more preferably, 0.8 μm or more and 2.5 μm or less). In the niobium carbide layer forming step **S105** described later, at least a part of the processing damage layer **21** becomes the niobium carbide layer **30**, so by setting the thickness of the processing damage layer **21** within the above range, it becomes easier to form the niobium carbide layer **30** with an appropriate thickness. When the thickness of the processing damage layer **21** is specified, for example, the processing damage layer **21** may be formed as a region in which the crystallite size is 10% or more smaller than the crystallite size of the niobium metal before the processing damage layer **21** is formed.

[0047] In the processing damage layer forming step **S102**, for example, it is preferable to introduce processing damage so that the crystallite size of the niobium metal in the processing damage layer **21** is 1 nm or more and 25 nm or less. When the crystallite size of the niobium metal in the processing damage layer **21** exceeds 25 nm, the carbon source **22** is unlikely to diffuse into the processing damage layer **21**, and it may be difficult to form a continuous niobium carbide layer **30**. In contrast, by setting the crystallite size of the niobium metal in the processing damage layer **21** to 25 nm or less, the surface area of the niobium metal becomes sufficiently large, making it easier to form the continuous niobium carbide layer **30**. Further, even when the crystallite size of the niobium metal in the processing damage layer **21** is less than 1 nm, it is technically difficult to decrease the crystallite size of niobium metal to less than 1 nm, and the cost increases significantly although it is possible to form the continuous niobium carbide layer **30**. Therefore, from the viewpoint of cost reduction, the crystallite size of the niobium metal in the processing damage layer **21** is preferably 1 nm or more.

(Carbon Source Embedding Step **S103**)

[0048] FIG. **3(b)** is a schematic view illustrating the carbon source embedding step **S103**. As illustrated in FIG. **3(b)**, the carbon source embedding step **S103** is a step of embedding a carbon source **22** comprising a solid carbon or carbon compound inside the processing damage layer **21** (for example, inside microcracks with voids). Since the processing damage layer **21** has a large number of microcracks, the carbon source **22** can be easily embedded therein. Specifically, for example, the surface of the substrate **20** is sprinkled with the carbon source **22**, and the surface is rubbed against another substrate **20** of the same size, whereby the carbon source **22** is embedded while being crushed until it is approximately the same size as the microcracks (for example, average particle size of 200 nm or less). Further, since the carbon source **22** is a solid, carbon atoms can be introduced into the processing damage layer **21** at a high concentration compared to a hydrocarbon gas, etc. This makes it easier for the carbon atoms to diffuse into the niobium metal of the processing damage layer **21**, making it easier to form the continuous niobium carbide layer **30**.

[0049] As the carbon source **22**, for example, graphite, boron carbide, diamond powder, etc., can be used. When diamond powder is used as the carbon source **22**, in order to enhance the reactivity with niobium metal, it is preferable to use diamond powder with at least its outer circumference covered with an amorphous layer (sp.^{sup.2} carbon). From the viewpoint of enhancing the reactivity with niobium metal and reducing a cost, it is preferable to use graphite as the carbon source **22**.

[0050] An average particle size of the carbon source **22** is preferably 200 nm or less. Thereby, it

becomes easier to embed the carbon source **22** inside the processing damage layer **21**. Further, the surface area of the carbon source **22** is increased, and the reactivity with niobium metal can be improved. A lower limit of the average particle size of the carbon source **22** is not particularly limited, but is, for example, 5 nm or more.

[0051] In the carbon source embedding step **S103**, when graphite (average particle size: 5 to 200 nm) is embedded in the processing damage layer **21** as the carbon source **22**, for example, it is preferable to embed the carbon source **22** of 0.1 $\mu\text{g}/\text{cm}^2$ or more and 10 $\mu\text{g}/\text{cm}^2$ or less. When the amount of the embedded carbon source **22** is less than 0.1 $\mu\text{g}/\text{cm}^2$, the carbonization of the niobium metal will be insufficient, and it may be difficult to form the continuous niobium carbide layer **30**. In contrast, by setting the amount of the embedded carbon source **22** to 0.1 $\mu\text{g}/\text{cm}^2$ or more, the niobium metal is sufficiently carbonized, and the continuous niobium carbide layer **30** is easily formed. On the other hand, when the amount of the embedded carbon source **22** exceeds 10 $\mu\text{g}/\text{cm}^2$, a large amount of carbon source **22** remains after the formation of the niobium carbide layer **30**, which may adversely affect the deposition of the conductive diamond film **40**. In contrast, by setting the amount of the embedded carbon source **22** to 10 $\mu\text{g}/\text{cm}^2$ or less, the amount of a residual carbon source **22** can be reduced. Further, from the viewpoint of reducing an energy (cost) required for embedding the carbon source **22**, it is preferable to embed the carbon source **22** to a depth of 1 μm or less. When checking the carbon source **22** inside the processing damage layer **21**, for example, the cross-section of the processing damage layer **21** (for example, at a depth of about 1 μm) may be observed using a transmission electron microscope.

(Seeding Step **S104**)

[0052] The seeding step **S104** is, for example, a step of seeding diamond particles on the main surface of the substrate **20** (the main surface on which the processing damage layer **21** is formed, that is, the surface of the processing damage layer **21**). By having the diamond particles present at an interface between the niobium carbide layer **30** and the conductive diamond film **40**, an energy barrier required for initial nucleation to form the conductive diamond film **40** can be lowered. The method for seeding with diamond particles can be a known method such as blasting or immersion.

[0053] The seeding step **S104** is preferably performed, for example, before the niobium carbide layer **30** is formed (that is, before the niobium carbide layer forming step **S105**). This allows the niobium carbide layer forming step **S105** and the diamond film depositing step **S106**, which will be described later, to be performed continuously within the same apparatus. Further, in this case, the seeding step **S104** may be performed simultaneously with the carbon source embedding step **S103** described above. That is, the carbon source **22** used in the carbon source embedding step **S103** and the diamond particles used in the seeding step **S104** can be the same diamond particles. As described above, the carbon source **22** preferably contains sp^2 carbon. Accordingly, diamond particles (e.g., nanodiamond particles obtained by detonation method) in which the circumference of a diamond structure (sp^3 structure) core part is covered with an amorphous layer (sp^2 carbon) are preferable because the sp^2 carbon is consumed during the formation of the niobium carbide layer **30**, leaving the sp^3 core as a seeded diamond particle.

[0054] The seeding step **S104** may be omitted. Even when the seeding step **S104** is omitted, by performing the above-described processing damage layer forming step **S102** and carbon source embedding step **S103**, the niobium carbide layer **30** that continuously covers the main surface of the substrate **20** can be formed in the niobium carbide layer forming step **S105**. That is, the occurrence of pinholes on the conductive diamond film **40** can be suppressed.

(Niobium Carbide Layer Forming Step **S105**)

[0055] The niobium carbide layer forming step **S105** is a step of forming a niobium carbide layer **30** that continuously covers the main surface of the substrate **20** by applying heat treatment to the processing damage layer **21** and causing the niobium metal to react with the carbon source **22**. Thereby, the occurrence of pinholes on the surface of the conductive diamond film **40**, can be

suppressed. In the niobium carbide layer forming step **S105**, a structure is reconstructed at the same time as the niobium carbide layer **30** is formed, and most of the microcracks formed in the processing damage layer forming step **S102** disappear. Further, in the processing damage layer **21** that remains without reacting with the carbon source **22**, the processing damage is recovered to a certain extent and the strength is increased, because defects disappear and decrease due to solid-phase diffusion at grain boundaries.

[0056] In the niobium carbide layer forming step **S105**, for example, a hot filament CVD apparatus described later can be used as a heating furnace for heat treatment to form the niobium carbide layer **30**.

[0057] The conditions for the heat treatment in the niobium carbide layer forming step **S105** are, for example, as follows. [0058] Heat treatment temperature (substrate temperature): 550 to 850 degrees [0059] Pressure: 10 to 50 Torr [0060] Heat treatment time: 30 to 120 minutes

[0061] In the niobium carbide layer forming step **S105**, it is preferable to form the niobium carbide layer **30** having a thickness of, for example, 10% to 100% (more preferably, 30% to 100%) of the processing damage layer **21**. In other words, it is preferable that a depth range from the surface to 10% or more of the thickness of the processing damage layer **21** is reacted with the carbon source **22** to form the niobium carbide layer **30**. When the thickness of the niobium carbide layer **30** is less than 10% of the thickness of the processing damage layer **21**, the nucleation density of the diamond crystals will be insufficient, which may cause pinholes. In contrast, by setting the thickness of the niobium carbide layer **30** to 10% or more of the thickness of the processing damage layer **21**, the nucleation density of the diamond crystals can be sufficiently increased. When an entire damaged layer **21** is reacted with the carbon source **22**, the thickness of the niobium carbide layer **30** becomes equal to the thickness of the damaged layer **21**.

[0062] In the niobium carbide layer forming step **S105**, for example, it is preferable to form the niobium carbide layer **30** containing niobium carbide of the chemical formula NbC as a main component. Thereby, the nucleation density of the diamond crystals for forming the conductive diamond film **40**, can be increased.

[0063] In the niobium carbide layer forming step **S105**, for example, it is preferable to form the niobium carbide layer **30** so that the crystallite size of the niobium carbide contained in the niobium carbide layer **30** is 1 nm or more and 60 nm or less. Thereby, it becomes easier to prevent pinholes from occurring.

(Diamond Film Depositing Step **S106**)

[0064] The diamond film depositing step **S106** is, for example, a step of depositing a conductive diamond film **40** on the niobium carbide layer **30**. According to this embodiment, the continuous niobium carbide layer **30** is formed in the above-described niobium carbide layer forming step **S105**, and therefore the occurrence of pinholes on the surface of the conductive diamond film **40** can be suppressed. In the diamond film depositing step **S106**, the conductive diamond film **40** can be deposited using, for example, a hot filament CVD apparatus. The hot filament CVD apparatus is configured so as to be able to supply various gases, such as hydrogen gas, carbon-containing gas, and boron-containing gas, to a growth chamber. The carbon-containing gas may be methane gas or ethane gas. The boron-containing gas may be trimethylboron (TMB) gas, trimethylborate gas, triethylborate gas, or diborane gas. Further, the hot filament CVD apparatus includes a temperature sensor, a tungsten filament, an electrode (for example, a molybdenum electrode) etc., in an airtight container arranged inside the growth chamber.

[0065] Diamond crystal growth conditions in the diamond film depositing step **S106** are exemplified as follows. [0066] Heat treatment temperature (substrate temperature): 700 to 1000 degrees [0067] Pressure: 5 to 50 Torr [0068] Heat treatment time: 1 to 10 hours

[0069] By the above steps, the diamond film-deposited substrate **10** can be manufactured. Also, the diamond film-deposited substrate **10** may be divided into pieces of a predetermined size to manufacture a plurality of diamond electrodes.

(3) Effects of this Embodiment

[0070] According to this embodiment, one or more of the following effects are achieved.

[0071] (a) In the diamond film-deposited substrate **10** of this embodiment, when the surface of the conductive diamond film **40** is observed using, for example, a scanning electron microscope, no pinholes reaching the substrate **20** or the niobium carbide layer **30** are present within a field of view of $20\ \mu\text{m} \times 20\ \mu\text{m}$. Thereby, even when a diamond electrode is used in a strongly acidic liquid, for example, the risk of the strongly acidic liquid coming into contact with the niobium carbide layer **30** can be reduced, thereby making it possible to improve the durability of the diamond electrode. From the viewpoint of further improving the durability of the diamond electrode, it is preferable that no pinholes reaching the substrate **20** or the niobium carbide layer **30** are present within a field of view of $1\ \text{mm} \times 1\ \text{mm}$, and it is particularly preferable that no pinholes are present over an entire surface of the conductive diamond film **40**.

[0072] Specifically, for example, when a diamond electrode for generating ozone water is manufactured using the diamond film-deposited substrate **10** of this embodiment, deterioration of the diamond electrode due to electrical conduction can be suppressed, and peeling of the conductive diamond film **40** can be prevented. That is, the durability of the diamond electrode can be improved.

[0073] (b) In the diamond film-deposited substrate **10** of this embodiment, when the cross section of the diamond film-deposited substrate **10** is observed using, for example, a scanning electron microscope, it is preferable that a continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is formed over a width of $20\ \mu\text{m}$ or more. Thereby, the nucleation density of diamond crystals for forming the conductive diamond film **40** can be sufficiently increased and the occurrence of pinholes can be suppressed. From the viewpoint of further suppressing the occurrence of pinholes, it is more preferable that the continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is formed over a width of $1\ \text{mm}$ or more, and it is particularly preferable that the continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is formed over an entire main surface of the substrate **20**.

[0074] (c) In the diamond film-deposited substrate **10** of this embodiment, the thickness of the niobium carbide layer **30** is preferably, for example, $0.5\ \mu\text{m}$ or more and $5\ \mu\text{m}$ or less (more preferably $0.8\ \mu\text{m}$ or more and $2.5\ \mu\text{m}$ or less). That is, a maximum thickness and a minimum thickness of the niobium carbide layer **30** are preferably within a range of $0.5\ \mu\text{m}$ or more and $5\ \mu\text{m}$ or less (more preferably, $0.8\ \mu\text{m}$ or more and $2.5\ \mu\text{m}$ or less). When the thickness of the niobium carbide layer **30** is less than $0.5\ \mu\text{m}$, the nucleation density of the diamond crystals for forming the conductive diamond film **40** may be insufficient. In contrast, by setting the thickness of the niobium carbide layer **30** to $0.5\ \mu\text{m}$ or more, the nucleation density of the diamond crystals for forming the conductive diamond film **40** can be sufficiently increased. On the other hand, when the thickness of the niobium carbide layer **30** exceeds $5\ \mu\text{m}$, the internal stress increases, and there is a possibility that the diamond film-deposited substrate **10** will be warped. In contrast, by setting the thickness of the niobium carbide layer **30** to $5\ \mu\text{m}$ or less, the internal stress can be reduced, and the warping of the diamond film-deposited substrate **10** can be reduced.

[0075] (d) In the diamond film-deposited substrate **10** of this embodiment, the main component of the niobium carbide layer **30** is preferably niobium carbide, for example, having a chemical formula NbC. Thereby, the nucleation density of the diamond crystals for forming the conductive diamond film **40** can be increased.

[0076] (e) In the diamond film-deposited substrate **10** of this embodiment, the crystallite size of the niobium carbide contained in the niobium carbide layer **30** is preferably, for example, $1\ \text{nm}$ or more and $60\ \text{nm}$ or less. When the crystallite size is outside the above range, it may be difficult to form the continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more. In contrast, by setting the crystallite size within the above range, the continuous niobium carbide layer **30** having a thickness of $0.5\ \mu\text{m}$ or more is easily formed, and as a result, the occurrence of pinholes is easily

suppressed.

[0077] (f) In the diamond film-deposited substrate **10** of this embodiment, the crystallite size of the niobium metal contained in the substrate **20** (particularly the niobium metal present in the vicinity of the interface with the niobium carbide layer **30**) is preferably, for example, 30 nm or more and 90 nm or less. When the crystallite size of the niobium metal is less than 30 nm, it may be difficult to form the continuous niobium carbide layer **30**. In contrast, by setting the crystallite size of the niobium metal to 30 nm or more, the continuous niobium carbide layer **30** is easily formed. On the other hand, when the crystallite size of the niobium metal exceeds 90 nm, the difference in crystallite size with respect to the niobium carbide contained in the niobium carbide layer **30** becomes large, and cracks, etc., may occur. In contrast, by setting the crystallite size of the niobium metal to 90 nm or less, the crystallite size is distributed so as to gradually decrease from the substrate **20** to the niobium carbide layer **30**, so the occurrence of cracks, etc., can be suppressed.

[0078] (g) A method for manufacturing the diamond film-deposited substrate **10** of this embodiment includes: for example, a process damage layer forming step **S102**, a carbon source embedding step **S103**, a niobium carbide layer forming step **S105**, and a diamond film depositing step **S106**. This allows the formation of the continuous niobium carbide layer **30**, making it possible to suppress the occurrence of pinholes on the surface of the conductive diamond film **40**.

[0079] (h) According to the method for manufacturing the diamond film-deposited substrate **10** of this embodiment, in the processing damage layer forming step **S102**, it is preferable to form the processing damage layer **21** having a thickness of, for example, 0.5 μm or more and 5 μm or less (more preferably, 0.8 μm or more and 2.5 μm or less). In the niobium carbide layer forming step **S105**, at least a portion of the processing damage layer **21** becomes the niobium carbide layer **30**, so by setting the thickness of the processing damage layer **21** within the above range, it becomes easier to form the niobium carbide layer **30** with an appropriate thickness.

[0080] (i) According to the method for manufacturing the diamond film-deposited substrate **10** of this embodiment, in the niobium carbide layer forming step **S105**, it is preferable to form the niobium carbide layer **30** having a thickness of, for example, 10% or more and 100% or less (more preferably, 30% or more and 100% or less) of the processing damage layer **21**. In other words, it is preferable that a depth range from the surface to 10% or more of the thickness of the processing damage layer **21** is reacted with the carbon source **22** to form the niobium carbide layer **30**. When the thickness of the niobium carbide layer **30** is less than 10% of the thickness of the processing damage layer **21**, the nucleation density of the diamond crystals will be insufficient, which may cause pinholes. In contrast, by setting the thickness of the niobium carbide layer **30** to 10% or more of the thickness of the processing damage layer **21**, the nucleation density of the diamond crystals can be sufficiently increased.

[0081] (j) According to the method for manufacturing the diamond film-deposited substrate **10** of this embodiment, in the processing damage layer forming step **S102**, for example, processing damage is preferably introduced so that the crystallite size of the niobium metal in the processing damage layer **21** is 1 nm or more and 25 nm or less. When the crystallite size of the niobium metal in the processing damage layer **21** exceeds 25 nm, the carbon source **22** is unlikely to diffuse into the processing damage layer **21**, and it may be difficult to form the continuous niobium carbide layer **30**. In contrast, by setting the crystallite size of the niobium metal in the processing damage layer **21** to 25 nm or less, the surface area of the niobium metal becomes sufficiently large, making it easier to form the continuous niobium carbide layer **30**. Further, even when the crystallite size of the niobium metal in the processing damage layer **21** is less than 1 nm, it is possible to form the continuous niobium carbide layer **30**. However, it is technically difficult to set the crystallite size of the niobium metal to less than 1 nm, and the cost increases significantly. Therefore, from the viewpoint of cost reduction, the crystallite size of the niobium metal in the processing damage layer **21** is preferably 1 nm or more.

[0082] (k) The method for manufacturing the diamond film-deposited substrate **10** of this

embodiment includes the seeding step **S104**. By having diamond particles present at the interface between the niobium carbide layer **30** and the conductive diamond film **40**, an energy barrier required for initial nucleation to form the conductive diamond film **40** can be lowered.

[0083] (1) The method for manufacturing the diamond film-deposited substrate **10** of this embodiment includes an unevenness forming step **S101**. Thereby, peeling caused by the difference in thermal expansion coefficient between the substrate **20** and the conductive diamond film **40** can be suppressed. That is, the peel strength of the diamond film-deposited substrate **10** can be improved.

(4) Modified Example of the First Embodiment

[0084] The above-described embodiment can be modified as required, as in the following modified examples. Hereinafter, only elements different from the above-described embodiment will be described, and elements substantially the same as those described in the above-described embodiment will be given the same reference numerals and their description will be omitted.

[0085] FIG. **4** is a schematic view illustrating the cross section of the diamond film-deposited substrate **10** of this modified example. As illustrated in FIG. **4**, the diamond film-deposited substrate **10** of this modified example has, for example, a substrate **20**, a niobium carbide layer **30**, and a conductive diamond film **40**, and the niobium carbide layer **30** can be divided into an upper portion **31** and a lower portion **32**.

[0086] The main component of the upper portion **31** of the niobium carbide layer **30** is niobium carbide having the chemical formula NbC, and the lower portion **32** of the niobium carbide layer **30** contains niobium carbide having the chemical formula Nb.sub.2C. Since the niobium carbide layer **30** is carbonized from the surface side, Nb.sub.2C with a high Nb content is likely to be formed in the lower portion **32** where the amount of carbon source **22** diffusing from the surface side is small. Even when the lower portion **32** of the niobium carbide layer **30** contains NbC as in this modified example, the formation of the continuous niobium carbide layer **30** can sufficiently increase the nucleation density of the diamond crystals for forming the conductive diamond film **40**, and can suppress the occurrence of pinholes, resulting in improving the durability of the diamond electrode.

[0087] The percentage of the thickness of the upper portion **31** and the lower portion **32** of the niobium carbide layer **30** is not particularly limited, but for example, the thickness of the lower portion **32** of the niobium carbide layer **30** is 50% or more and 150% or less of the thickness of the upper portion **31**.

[0088] The crystallite size of the niobium carbide contained in the upper portion **31** of the niobium carbide layer **30** is smaller than the crystallite size of the niobium carbide contained in the lower portion **32**. Specifically, for example, the crystallite size of the niobium carbide contained in the upper portion **31** is 1 nm or more and 25 nm or less, and the crystallite size of the niobium carbide contained in the lower portion **32** is, for example, 20 nm or more and 60 nm or less. The crystallite size of the niobium carbide contained in the upper portion **31** was calculated from the peak of NbC (111) in XRD, and the crystallite size of the niobium carbide contained in the lower portion **32** was calculated from the peak of Nb.sub.2C (211) in XRD.

[0089] In the niobium carbide layer forming step **S105** of this modified example, the main component of the upper portion **31** of the niobium carbide layer **30** is niobium carbide having the chemical formula NbC, and the niobium carbide layer **30** is formed such that the lower portion **32** of the niobium carbide layer **30** contains niobium carbide having the formula Nb.sub.2C. The smaller the crystallite size of the niobium metal, the easier it is to carbonize and form NbC. Therefore, when forming the niobium carbide layer **30** as in this modified example, for example, in the processing damage layer forming step **S102**, processing damage may be introduced so that the crystallite size of the niobium metal in the upper portion of the processing damage layer **21** is smaller than the crystallite size of the niobium metal in the lower portion thereof.

Other Embodiments of the Present Invention

[0090] Although the embodiment of the present invention has been specifically described above, the present invention is not limited to the above-described embodiment, and various modifications can be made without departing from the gist of the present invention.

[0091] For example, in the above embodiment, each step of the method for manufacturing the diamond film-deposited substrate **10** has been described, but it is not necessary to perform all of the steps described above. Specifically, for example, one (or both) of the unevenness forming step **S101** and the seeding step **S104** may be omitted. In this case also, similarly to the first embodiment, the continuous niobium carbide layer **30** is formed, and pinholes in the conductive diamond film **40** can be suppressed.

[0092] In the above embodiment, the carbon source **22** is embedded inside the microcracks with voids in the carbon source embedding step **S103**. However, it is not always necessary to form microcracks with voids and embed the carbon source **22** inside the microcracks. For example, by making the crystallite size of the niobium metal in the processing damage layer **21** sufficiently small (for example, 20 nm or less), it is possible to form a large number of grain boundaries (microcracks without voids) where crystal defects are densely gathered and arranged. Thereby, a diffusion path of the carbon source **22** can be sufficiently secured and the surface area of the niobium metal that contributes to the carbonization reaction can be sufficiently increased. Therefore, even when the carbon source **22** is not embedded inside the microcracks but is introduced to be in contact with the surface of the processing damage layer **21**, the niobium carbide layer **30** can be formed. The carbon source **22** diffuses into the inside of the niobium metal through grain boundaries (microcracks without voids) even when it is not embedded inside the microcracks with voids. Therefore, it is possible to obtain a niobium carbide layer **30** having a thickness according to the diffusion length. However, from the viewpoint of facilitating the formation of the continuous niobium carbide layer **30** having a sufficient thickness (for example, 0.5 μm or more), as in the above embodiment, it is preferable to embed the carbon source **22** inside the microcracks with voids.

[0093] Further, the above-described embodiment shows a case in which the conductive diamond film **40** has a single layer structure. However, the conductive diamond film **40** may have a layered structure in which a plurality of conductive diamond layers are stacked. However, according to the present invention, even when the conductive diamond film **40** has a single-layer structure as in the above-described embodiment, the occurrence of pinholes can be suppressed.

Examples

[0094] Next, examples of the present invention will be described. These examples are merely examples of the present invention, and the present invention is not limited to these examples.

(1) Manufacturing of the Diamond Film-Deposited Substrate **10**

(Sample 1)

[0095] First, the diamond film-deposited substrate **10** of Sample 1 was manufactured by the following procedure.

[0096] A substrate **20** comprising niobium metal was prepared and subjected to grinding process. For the grinding process, a vertical shaft round table type device was used, and a grindstone made of cubic boron carbide (grain size #600 or more) was used. It was confirmed by a scanning electron microscope that a processing damage layer **21** having microcracks was formed on the main surface of the substrate **20** after the grinding process.

[0097] After the grinding process, the main surface of the substrate **20** was sprinkled with 7.5 mg/cm² of graphite (particle size 1 to 2 μm) as the carbon source **22**, and the surface was rubbed against another substrate **20** of the same size. The amount of embedded graphite was measured before and after embedding, and it was confirmed that 2.1 $\mu\text{g/cm}^2$ of graphite (grain size 5 to 45 nm) was embedded inside the processing damage layer **21** after rubbing. When the main surface of the substrate **20** was measured by XRD, the crystallite size of the niobium metal in the processing damage layer **21** was 12.3 nm.

[0098] In these examples, the crystallite sizes were calculated from the results of wide-angle X-ray diffraction measurement using an X-ray diffractometer (RINT2500HLB) manufactured by Rigaku Corporation. The measurement conditions were as follows: [0099] Measurement wavelength: CuK α (0.15418 nm) [0100] X-ray output: 50 kV-250 mA [0101] Optical system: Parallel beam with monochromator [0102] Divergence slit (DS): 0.5°+10 mmH [0103] Scattering slit (SS): 0.5° [0104] Receiving slit (RS): 0.15 mm [0105] Scan axis: 2 θ / θ [0106] Scanning method: Continuous scanning [0107] Scanning range: 5° $\leq$ 2 θ $\leq$ 100° [0108] Scanning speed: 0.5°/min [0109] Sampling: 0.01°

[0110] The substrate **20** with the graphite embedded therein was placed in a hot filament CVD apparatus, and the formation of the niobium carbide layer **30** and the deposition of the conductive diamond film **40** were performed successively. Specifically, hydrogen gas, methane gas, and TMB gas were introduced, and a pressure was set to 20 to 50 Torr. Thereafter, a voltage (120 to 150 V) was applied to the 40 cm filament and maintained until the filament was carbonized and the resistance became constant. Further, the filament voltage was increased to 175V, and a filament temperature was kept at 2200 to 2400° C. and a substrate temperature was kept at 700 to 800° C. for 180 minutes.

[0111] The diamond film-deposited substrate **10** was removed from the hot filament CVD apparatus, and it was confirmed that the conductive diamond film **40** with a thickness of 3.32 μ m had been deposited thereon. Further, when the diamond film-deposited substrate **10** was measured from the conductive diamond film **40** side by XRD, the crystallite size of the niobium metal was 85.6 nm, and the crystallite size of the niobium carbide was 1.9 nm.

(Sample 2)

[0112] Further, the diamond film-deposited substrate **10** of Sample 2 was manufactured by the following procedure.

[0113] The substrate **20** comprising niobium metal was prepared, and subjected to the same grinding process as in Sample 1. It was confirmed by a scanning electron microscope that the processing damage layer **21** having microcracks was formed on the main surface of the substrate **20** after the grinding process.

[0114] In Sample 2, the carbon source **22** was not embedded, and the substrate **20** after grinding was placed in a hot filament CVD apparatus, and the formation of the niobium carbide layer **30** and the deposition of the conductive diamond film **40** were performed successively under the same conditions as those for Sample 1.

[0115] The diamond film-deposited substrate **10** was removed from the hot filament CVD apparatus, and it was confirmed that the conductive diamond film **40** with a thickness of 2.72 μ m had been deposited thereon. Further, when the diamond film-deposited substrate **10** was measured from the conductive diamond film **40** side by XRD, the crystallite size of the niobium metal was 33.0 nm, and the crystallite size of the niobium carbide was 6.9 nm.

(Sample 3)

[0116] Further, the diamond film-deposited substrate **10** of Sample 3 was manufactured by the following procedure.

[0117] In Sample 3, without forming the processing damage layer **21**, graphite (particle size 1 to 2 μ m) was sprinkled as a carbon source **22** in an amount of 7.5 mg/cm² on the main surface of a substrate **20** comprising metal niobium, and the surface was rubbed against another substrate **20** of the same size. It was confirmed that 1.2 μ g/cm² of graphite was adhered to the surface of the substrate **20** after rubbing. When the main surface of the substrate **20** was measured by XRD, the crystallite size of the niobium metal was 26.1 nm.

[0118] The substrate **20** after rubbing was placed in a hot filament CVD apparatus, and under the same conditions as those for sample 1, the formation of the niobium carbide layer **30** and the deposition of the conductive diamond film **40** were performed successively.

[0119] The diamond film-deposited substrate **10** was removed from the hot filament CVD

apparatus, and it was confirmed that the conductive diamond film **40** with a thickness of 2.94 μm had been deposited thereon. Further, when the diamond film-deposited substrate **10** was measured from the conductive diamond film **40** side by XRD, the crystallite size of the niobium metal was 58.1 nm, and the crystallite size of the niobium carbide was 25.7 nm.

(Sample 4)

[0120] Further, the diamond film-deposited substrate **10** of Sample 4 was manufactured by the following procedure.

[0121] The substrate **20** comprising metal niobium was prepared and subjected to blast processing. For the blast processing, a silicon carbide (grain size #100) shot material was used. It was confirmed by a scanning electron microscope that a processing damage layer **21** having microcracks was formed on the main surface of the substrate **20** after the grinding process.

[0122] After the blasting process, the main surface of the substrate **20** was sprinkled with 7.5 mg/cm² of graphite (particle size 1 to 2 μm) as the carbon source **22**, and the surface was rubbed against another substrate **20** of the same size. The amount of the embedded graphite was measured before and after embedding, and it was confirmed that 5.3 $\mu\text{g/cm}^2$ of graphite (grain size 5 to 70 nm) was embedded inside the processing damage layer **21** after rubbing. When the main surface of the substrate **20** was measured by XRD, the crystallite size of the niobium metal in the processing damage layer **21** was 6.9 nm.

[0123] The substrate **20** with the graphite embedded therein was placed in a hot filament CVD apparatus, and under the same conditions as those for sample 1, the formation of the niobium carbide layer **30** and the deposition of the conductive diamond film **40** were performed successively.

[0124] The diamond film-deposited substrate **10** was removed from the hot filament CVD apparatus, and it was confirmed that the conductive diamond film **40** with a thickness of 3.21 μm had been deposited thereon. Further, when the diamond film-deposited substrate **10** was measured from the conductive diamond film **40** side by XRD, the crystallite size of the niobium metal was 63.1 nm, and the crystallite size of the niobium carbide was 12.8 nm.

(2) Evaluation of the Diamond Film-Deposited Substrate **10**

[0125] The cross sections of Samples 1 to 4 were observed using a scanning electron microscope. In sample 2 in which the carbon source **22** was not embedded and sample 3 in which the processing damage layer **21** was not formed, niobium carbide formed in an island shape was observed at the interface between the substrate **20** and the conductive diamond film **40**, and a continuous niobium carbide layer **30** was not formed. In contrast, in Sample 1 and Sample 4, in which the processing damage layer **21** was formed and the carbon source **22** was embedded in the processing damage layer **21**, the continuous niobium carbide layer **30** was formed at the interface between the substrate **20** and the conductive diamond film **40**.

[0126] Further, for Samples 1 to 4, the surface of the conductive diamond film **40** was observed using a scanning electron microscope. A surface photograph of Sample 1 is shown in FIG. 5(a), a surface photograph of Sample 2 is shown in FIG. 5(b), a surface photograph of Sample 3 is shown in FIG. 5(c), and a surface photograph of Sample 4 is shown in FIG. 5(d).

[0127] As shown in FIG. 5(b) and FIG. 5(c), in Sample 2 in which the carbon source **22** was not embedded and Sample 3 in which the processing damage layer **21** was not formed, pinholes were observed on the surface of the conductive diamond film **40**. In contrast, as shown in FIG. 5(a) and FIG. 5(d), in Sample 1 and Sample 4, in which the processing damage layer **21** was formed and the carbon source **22** was embedded in the processing damage layer **21**, no pinholes were observed on the surface of the conductive diamond film **40**.

[0128] As described above, it was confirmed that the processing damage layer **21** having microcracks was formed on the main surface of the substrate **20**, and the carbon source **22** was embedded inside the processing damage layer **21**, thereby forming the continuous niobium carbide layer **30**. It was also confirmed that due to the formation of the continuous niobium carbide layer

30, the occurrence of pinholes on the surface of the conductive diamond film **40** could be suppressed.

(3) Durability Test of the Diamond Electrode

[0129] The diamond electrodes fabricated from the diamond film-deposited substrates **10** of Samples 1 to 4 were used as the anode and cathode, respectively, to perform a durability test for generating ozone water. Nafion 324 (manufactured by Du Pont) was used as a polymer electrolyte membrane. Tap water (flow rate 200 mL/min) was used as raw water, and a cycle of driving for 8 minutes at a low voltage of 15 V and then pausing for 2 minutes was repeated 1000 times.

Thereafter, the diamond electrode was taken out and an area percentage of the peeled-off conductive diamond film **40** was confirmed. The results are shown in Table 1.

TABLE-US-00001

Sample	concentration at first cycle (ppm)	Peeling area after 1000 cycles (%)	concentration after 1000 cycles (ppm)
Sample 1	11.3	0%	10.8
Sample 2	9.3	About 80%	1.5
Sample 3	8.3	About 90%	1.0
Sample 4	12.1	0%	11.5

[0130] As shown in Table 1, in Sample 2 in which the carbon source **22** was not embedded and in Sample 3 in which the processing damage layer **21** was not formed, the ozone water concentration at the 1000th cycle was significantly lower than that at the first cycle, and degradation due to electrical current was confirmed. Further, peeling of the conductive diamond film **40** was also confirmed. In contrast, in Sample 1 and Sample 4, in which the processing damage layer **21** was formed and the carbon source **22** was embedded in the processing damage layer **21**, even after 1000 cycles, the ozone water concentration was the same (95% or more) as that after the first cycle. Further, no peeling of the conductive diamond film **40** was observed.

[0131] As described above, it was confirmed that by forming the continuous niobium carbide layer **30** and suppressing the occurrence of pinholes on the surface of the conductive diamond film **40**, deterioration due to electrical current could be suppressed and peeling of the conductive diamond film **40** could be prevented. That is, it was confirmed that the durability of the diamond electrode was improved.

<Preferable Aspects of the Present Invention>

(Supplementary Description 1)

[0132] According to an aspect of the present invention, there is provided a diamond film-deposited substrate, including: [0133] a substrate comprising niobium metal; [0134] a niobium carbide layer on at least one main surface of the substrate; and [0135] a conductive diamond film on the niobium carbide layer, [0136] wherein when a surface of the conductive diamond film is observed using a scanning electron microscope, no pinholes reaching the substrate or the niobium carbide layer are present within a field of view of 20 μm ×20 μm .

[0137] Particularly preferably, no pinholes reaching the substrate or the niobium carbide layer are present over an entire surface of the conductive diamond film.

(Supplementary Description 2)

[0138] There is provided the diamond film-deposited substrate according to the supplementary description 1, [0139] wherein when a cross section of the diamond film-deposited substrate is observed with a scanning electron microscope, a continuous niobium carbide layer having a thickness of 0.5 μm or more is provided over a width of 20 μm or more.

[0140] More preferably, a continuous niobium carbide layer having a thickness of 0.5 μm or more is provided over a width of 1 mm or more.

[0141] Particularly preferably, a continuous niobium carbide layer having a thickness of 0.5 μm or more is provided on an entire main surface.

(Supplementary Description 3)

[0142] There is provided the diamond film-deposited substrate according to the supplementary description 1 or 2, [0143] wherein the niobium carbide layer has a thickness of 0.5 μm or more and 5 μm or less.

[0144] More preferably, the niobium carbide layer has a thickness of 0.8 μm or more and 2.5 μm or

less.

(Supplementary Description 4)

[0145] There is provided the diamond film-deposited substrate according to any one of the supplementary descriptions 1 to 3, [0146] wherein a main component of the niobium carbide layer is niobium carbide having a chemical formula NbC.

(Supplementary Description 5)

[0147] There is provided the diamond film-deposited substrate according to any one of the supplementary descriptions 1 to 4, [0148] wherein a main component of an upper portion of the niobium carbide layer is niobium carbide having a chemical formula NbC, and a lower portion of the niobium carbide layer comprises niobium carbide having a chemical formula Nb.sub.2C.

(Supplementary Description 6)

[0149] There is provided the diamond film-deposited substrate according to any one of the supplementary descriptions 1 to 5, [0150] wherein a crystallite size of the niobium carbide contained in the niobium carbide layer is 1 nm or more and 60 nm or less.

(Supplementary Description 7)

[0151] There is provided the diamond film-deposited substrate according to any one of the supplementary descriptions 1 to 6, [0152] wherein a crystallite size of the niobium metal is 30 nm or more and 90 nm or less.

(Supplementary Description 8)

[0153] There is provided a method for manufacturing a diamond film-deposited substrate, the method including: [0154] forming a processing damage layer having microcracks by introducing processing damage onto at least one main surface of a substrate comprising niobium metal; [0155] embedding a carbon source comprising a solid carbon or carbon compound into the processing damage layer; [0156] applying a heat treatment to the processing damage layer to cause a reaction between the niobium metal and the carbon source to form a niobium carbide layer continuously covering the main surface; and [0157] depositing a conductive diamond film on the niobium carbide layer.

(Supplementary Description 9)

[0158] There is provided the method for manufacturing a diamond film-deposited substrate according to the supplementary description 8, [0159] wherein in the forming the processing damage layer, a processing damage layer having a thickness of 0.5 μm or more and 5 μm or less is formed. [0160] more preferably, a processing damage layer having a thickness of 0.8 μm or more and 2.5 μm or less is formed.

(Supplementary Description 10)

[0161] There is provided the method for manufacturing a diamond film-deposited substrate according to the supplementary description 8 or 9, [0162] wherein in the forming the niobium carbide layer, a niobium carbide layer having a thickness that is 10% or more and 100% or less of the processing damage layer is formed. [0163] more preferably, a niobium carbide layer having a thickness of 30% or more and 100% or less of the processing damage layer is formed.

(Supplementary Description 11)

[0164] There is provided the method for manufacturing a diamond film-deposited substrate according to any one of the supplementary descriptions 8 to 10, [0165] wherein in the forming the processing damage layer, processing damage is introduced so that a crystallite size of the niobium metal in the processing damage layer is 1 nm or more and 25 nm or less.

(Supplementary Description 12)

[0166] There is provided the method for manufacturing a diamond film-deposited substrate according to any one of the supplementary descriptions 8 to 11, [0167] wherein the method further includes seeding the main surface with diamond particles before forming the niobium carbide layer.

(Supplementary Description 13)

[0168] There is provided the method for manufacturing a diamond film-deposited substrate

according to any one of the supplementary descriptions 8 to 12, [0169] wherein the method further includes performing processing to form unevenness on the main surface before forming the processing damage layer.

(Supplementary Description 14)

[0170] There is provided a method for manufacturing a diamond film-deposited substrate according to any one of the supplementary descriptions 8 to 13, [0171] wherein in the forming the niobium carbide layer, a niobium carbide layer containing niobium carbide of a chemical formula NbC as a main component is formed.

(Supplementary Description 15)

[0172] There is provided a method for manufacturing a diamond film-deposited substrate according to any one of the supplementary descriptions 8 to 13, [0173] wherein in the forming the niobium carbide layer, the niobium carbide layer is formed so that a main component of an upper portion of the niobium carbide layer is niobium carbide having a chemical formula NbC, and a lower portion of the niobium carbide layer contains niobium carbide having a chemical formula Nb.sub.2C.

(Supplementary Description 16)

[0174] There is provided a method for manufacturing a diamond film-deposited substrate according to any one of the supplementary descriptions 8 to 15, [0175] wherein in the forming the niobium carbide layer, the niobium carbide layer is formed so that a crystal grain size of niobium carbide contained in the niobium carbide layer is 1 nm or more and 60 nm or less.

DESCRIPTION OF SIGNS AND NUMERALS

[0176] **10** Diamond film-deposited substrate [0177] **20** Substrate [0178] **21** Processing damage layer [0179] **22** Carbon source [0180] **30** Niobium carbide layer [0181] **31** Upper portion [0182] **32** Lower portion [0183] **40** Conductive diamond film [0184] **S101** Unevenness forming step [0185] **S102** Processing damage layer forming step [0186] **S103** Carbon source embedding step [0187] **S104** Seeding step [0188] **S105** Niobium carbide layer forming step [0189] **S106** Diamond film depositing step

Claims

1. According to an aspect of the present invention, there is provided a diamond film-deposited substrate, comprising: a substrate comprising niobium metal; a niobium carbide layer on at least one main surface of the substrate; and a conductive diamond film on the niobium carbide layer, wherein when a surface of the conductive diamond film is observed using a scanning electron microscope, no pinholes reaching the substrate or the niobium carbide layer are present within a field of view of 20 μm ×20 μm .
2. The diamond film-deposited substrate according to claim 1, wherein when a cross section of the diamond film-deposited substrate is observed with a scanning electron microscope, a continuous niobium carbide layer having a thickness of 0.5 μm or more is provided over a width of 20 μm or more.
3. The diamond film-deposited substrate according to claim 1, wherein the niobium carbide layer has a thickness of 0.5 μm or more and 5 μm or less.
4. The diamond film-deposited substrate according to claim 1, wherein a main component of the niobium carbide layer is niobium carbide having a chemical formula NbC.
5. The diamond film-deposited substrate according to claim 1, wherein a main component of an upper portion of the niobium carbide layer is niobium carbide having a chemical formula NbC, and a lower portion of the niobium carbide layer comprises niobium carbide having a chemical formula Nb.sub.2C.
6. The diamond film-deposited substrate according to claim 1, wherein a crystallite size of the niobium carbide contained in the niobium carbide layer is 1 nm or more and 60 nm or less.
7. The diamond film-deposited substrate according to claim 1, wherein a crystallite size of the

niobium metal is 30 nm or more and 90 nm or less.

8. A method for manufacturing a diamond film-deposited substrate, the method including: forming a processing damage layer having microcracks by introducing processing damage onto at least one main surface of a substrate comprising niobium metal; embedding a carbon source comprising a solid carbon or carbon compound into the processing damage layer; applying a heat treatment to the processing damage layer to cause a reaction between the niobium metal and the carbon source to form a niobium carbide layer continuously covering the main surface; and depositing a conductive diamond film on the niobium carbide layer.

9. The method for manufacturing a diamond film-deposited substrate according to claim 8, wherein in the forming the processing damage layer, a processing damage layer having a thickness of 0.5 μm or more and 5 μm or less is formed.

10. The method for manufacturing a diamond film-deposited substrate according to claim 8, wherein in the forming the niobium carbide layer, a niobium carbide layer having a thickness that is 10% or more and 100% or less of the processing damage layer is formed.

11. The method for manufacturing a diamond film-deposited substrate according to claim 8, wherein in the forming the processing damage layer, processing damage is introduced so that a crystallite size of the niobium metal in the processing damage layer is 1 nm or more and 25 nm or less.

12. The method for manufacturing a diamond film-deposited substrate according to claim 8, wherein the method further includes seeding the main surface with diamond particles before forming the niobium carbide layer.

13. The method for manufacturing a diamond film-deposited substrate according to claim 8, wherein the method further includes performing processing to form unevenness on the main surface before forming the processing damage layer.
