

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412893
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Momma; Yohei et al.

Method for forming positive electrode active material

Abstract

A method for forming a positive electrode active material of a lithium ion secondary battery is provided. In the method for forming a positive electrode active material, a first container that includes a mixture of lithium oxide, fluoride, and a magnesium compound and fluoride that is outside the first container are provided in a heating furnace, and the heating furnace is heated at a temperature higher than or equal to a temperature at which the fluoride is volatilized or sublimated. It is further preferable that the fluoride be lithium fluoride and the magnesium compound be magnesium fluoride.

Inventors:	Momma; Yohei (Kanagawa, JP), Ochiai; Teruaki (Kanagawa, JP), Mikami; Mayumi (Kanagawa, JP), Saito; Jo (Kanagawa, JP), Takahashi; Masahiro (Kanagawa, JP)
Applicant:	SEMICONDUCTOR ENERGY LABORATORY CO., LTD. (Atsugi, JP)
Family ID:	72667091
Assignee:	Semiconductor Energy Laboratory Co., Ltd. (Atsugi, JP)
Appl. No.:	17/442195
Filed (or PCT Filed):	March 23, 2020
PCT No.:	PCT/IB2020/052665
PCT Pub. No.:	WO2020/201892
PCT Pub. Date:	October 08, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20220190332 A1	Jun. 16, 2022

Foreign Application Priority Data

JP 2019-072816 Apr. 05, 2019

Publication Classification

Int. Cl.: H01M4/525 (20100101); C01G51/66 (20250101); H01G11/50 (20130101); H01G11/86 (20130101); H01M4/04 (20060101); H01M4/02 (20060101)

U.S. Cl.:

CPC H01M4/525 (20130101); C01G51/66 (20130101); H01G11/50 (20130101); H01G11/86 (20130101); H01M4/0471 (20130101); C01P2002/77 (20130101); C01P2002/88 (20130101); C01P2006/40 (20130101); H01M2004/028 (20130101)

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8741484	12/2013	Karthikeyan et al.	N/A	N/A
8765306	12/2013	Amiruddin et al.	N/A	N/A
8916294	12/2013	Kumar et al.	N/A	N/A
10741845	12/2019	Yushin et al.	N/A	N/A
11539039	12/2021	Chae et al.	N/A	N/A
2002/0110736	12/2001	Kweon et al.	N/A	N/A
2003/0104279	12/2002	Miyazaki et al.	N/A	N/A
2004/0142241	12/2003	Nagayama	N/A	N/A
2006/0263690	12/2005	Suhara	429/231.6	H01M4/525
2007/0117014	12/2006	Saito et al.	N/A	N/A
2008/0241693	12/2007	Fukuchi et al.	N/A	N/A
2009/0087362	12/2008	Sun et al.	N/A	N/A
2009/0104532	12/2008	Hosoya	N/A	N/A
2010/0086854	12/2009	Kumar et al.	N/A	N/A
2010/0247986	12/2009	Toyama et al.	N/A	N/A
2011/0236751	12/2010	Amiruddin et al.	N/A	N/A
2011/0244331	12/2010	Karthikeyan et al.	N/A	N/A
2011/0300441	12/2010	Kawakami	N/A	N/A
2013/0052534	12/2012	Fujiki et al.	N/A	N/A
2013/0323596	12/2012	Morita et al.	N/A	N/A
2016/0013478	12/2015	Satow et al.	N/A	N/A
2016/0276659	12/2015	Choi et al.	N/A	N/A
2017/0018768	12/2016	Yushin et al.	N/A	N/A

2017/0069911	12/2016	Volkov et al.	N/A	N/A
2018/0013130	12/2017	Ochiai et al.	N/A	N/A
2018/0145317	12/2017	Momma et al.	N/A	N/A
2018/0145368	12/2017	Ochiai et al.	N/A	N/A
2018/0233770	12/2017	Ein-eli et al.	N/A	N/A
2020/0176770	12/2019	Takahashi et al.	N/A	N/A
2020/0313177	12/2019	Momma et al.	N/A	N/A
2020/0313178	12/2019	Momma et al.	N/A	N/A
2020/0328413	12/2019	Momma et al.	N/A	N/A
2020/0358091	12/2019	Momma et al.	N/A	N/A
2020/0373567	12/2019	Momma et al.	N/A	N/A
2020/0373568	12/2019	Momma et al.	N/A	N/A
2020/0373569	12/2019	Momma et al.	N/A	N/A
2020/0373580	12/2019	Yushin et al.	N/A	N/A
2021/0020935	12/2020	Takahashi et al.	N/A	N/A
2021/0028456	12/2020	Takahashi et al.	N/A	N/A
2021/0083281	12/2020	Mikami et al.	N/A	N/A
2021/0313571	12/2020	Momma et al.	N/A	N/A
2022/0199984	12/2021	Momma et al.	N/A	N/A
2022/0199989	12/2021	Momma et al.	N/A	N/A
2023/0307622	12/2022	Momma et al.	N/A	N/A
2023/0327095	12/2022	Momma et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
105655554	12/2015	CN	N/A
106029577	12/2015	CN	N/A
108023068	12/2017	CN	N/A
3460882	12/2018	EP	N/A
3783707	12/2020	EP	N/A
2000-203842	12/1999	JP	N/A
2001210325	12/2000	JP	N/A
2002-216760	12/2001	JP	N/A
2010-080407	12/2009	JP	N/A
2012-018914	12/2011	JP	N/A
2012-504316	12/2011	JP	N/A
2013-524413	12/2012	JP	N/A
2013-524440	12/2012	JP	N/A
2015-099722	12/2014	JP	N/A
2016-076454	12/2015	JP	N/A
2018-088400	12/2017	JP	N/A
2018-520488	12/2017	JP	N/A
2018-523276	12/2017	JP	N/A
2019-032954	12/2018	JP	N/A
7081908	12/2021	JP	N/A
2011-00769554	12/2010	KR	N/A
201907608	12/2018	TW	N/A
WO-2010/039732	12/2009	WO	N/A
WO-2010039732	12/2009	WO	C01G 53/50

WO-2011/119386	12/2010	WO	N/A
WO-2011/123264	12/2010	WO	N/A
WO2015128219	12/2014	WO	N/A
WO-2015128219	12/2014	WO	C01G 53/50
WO-2017/011594	12/2016	WO	N/A
WO-2017/025957	12/2016	WO	N/A
WO-2018/135929	12/2017	WO	N/A
WO-2019/003025	12/2018	WO	N/A

OTHER PUBLICATIONS

International Search Report (Application No. PCT/IB2020/052665) Dated Jun. 30, 2020. cited by applicant

Written Opinion (Application No. PCT/IB2020/052665) Dated Jun. 30, 2020. cited by applicant

Motohashi.T et al., “Electronic phase diagram of the layered cobalt oxide system Li_xCoO_2 ($0.0 \leq x \leq 1.0$)”, Phys. Rev. B (Physical Review. B), Oct. 9, 2009, vol. 80, No. 16, pp. 165114-1-165114-9. cited by applicant

Okumura.T et al., “Correlation of lithium ion distribution and X-ray absorption near-edge structure in O3- and O2-lithium cobalt oxides from first-principle calculation”, Journal of Materials Chemistry, 2012, vol. 22, pp. 17340-17348. cited by applicant

Exhibit 1031 of IPR2023-01016, portions of JP-2012-018914A and Full translation. cited by applicant

Exhibit 1027 of IPR2023-01349, Full translation of JP-2012-018914A. cited by applicant

Chinese Office Action (Application No. 202080026420.0) Dated Apr. 28, 2023. cited by applicant

Appendix B of EPR U.S. Appl. No. 90/019,535, portions of JP-2012-018914A and Full translation. cited by applicant

Exhibit 1040 of EPR U.S. Appl. No. 90/019,535, JP-2012-018914A and Full translation. cited by applicant

Primary Examiner: Davis; Sheng H

Attorney, Agent or Firm: Fish & Richardson P.C.

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS

(1) This application is a U.S. National Phase Application under 35 U.S.C. § 371 of International Application PCT/IB2020/052665, filed on Mar. 23, 2020, which is incorporated by reference and claims the benefit of a foreign priority application filed in Japan on Apr. 5, 2019, as Application No. 2019-072816.

TECHNICAL FIELD

(2) One embodiment of the present invention relates to a method for forming a positive electrode active material. Alternatively, the present invention relates to an object, a process, a machine, manufacture, or a composition (composition of matter). One embodiment of the present invention relates to a semiconductor device, a display device, a light-emitting device, a power storage device, a lighting device, an electronic device, or a forming method thereof.

(3) Note that in this specification, a power storage device refers to every element and device having a function of storing electric power. Examples of the power storage device include a storage battery (also referred to as a secondary battery) such as a lithium ion secondary battery, a lithium ion

capacitor, an all-solid-state battery, and an electric double layer capacitor.

(4) In addition, electronic devices in this specification mean all devices including power storage devices, and electro-optical devices including power storage devices, information terminal devices including power storage devices, and the like are all electronic devices.

BACKGROUND ART

(5) In recent years, a variety of power storage devices such as lithium ion secondary batteries, lithium ion capacitors, air batteries, and all-solid-state batteries have been actively developed. In particular, a demand for lithium ion secondary batteries with high output and high capacity has rapidly grown with the development of the semiconductor industry, for portable information terminals such as mobile phones, smartphones, and laptop computers; portable music players; digital cameras; medical equipment; next-generation clean energy vehicles such as hybrid vehicles (HV), electric vehicles (EV), and plug-in hybrid electric vehicles (PHV or PHEV); and the like. The lithium ion secondary batteries are essential as rechargeable energy supply sources for today's information society.

(6) Thus, improvement of a positive electrode active material has been studied to increase the cycle performance and the capacity of the lithium ion secondary battery (Patent Document 1 and Patent Document 2).

(7) The performance currently required for power storage devices includes safe operation under a variety of environments and longer-term reliability.

REFERENCE

Patent Documents

(8) [Patent Document 1] Japanese Published Patent Application No. 2012-018914 [Patent Document 2] Japanese Published Patent Application No. 2016-076454

Non-Patent Documents

(9) [Non-Patent Document 1] Toyoki Okumura et al., "Correlation of lithium ion distribution and X-ray absorption near-edge structure in O3- and O2-lithium cobalt oxides from first-principle calculation", *Journal of Materials Chemistry*, 2012, 22, pp. 17340-17348. [Non-Patent Document 2] T. Motohashi, et al., "Electronic phase diagram of the layered cobalt oxide system $\text{Li}_{1-x}\text{CoO}_2$ ($0.0 \leq x \leq 1.0$)", *Physical Review B*, 80 (16); 165114.

SUMMARY OF THE INVENTION

Problems to be Solved by the Invention

(10) A lithium ion secondary battery and a positive electrode active material that is used for it require an improvement in terms of capacity, cycle performance, charge and discharge characteristics, reliability, and safety, and development of a lithium composite oxide LiMO_2 in which part of LiCoO_2 is substituted with different elements progresses. Furthermore, development of a method for forming LiMO_2 at low cost in a short time is desired.

(11) In view of the above, one object of one embodiment of the present invention is to provide a method for forming a positive electrode active material. Another object of one embodiment of the present invention is to provide a novel positive electrode active material. Another object of one embodiment of the present invention is to provide a novel power storage device.

(12) Note that the description of these objects does not preclude the existence of other objects. One embodiment of the present invention does not have to achieve all these objects. Note that other objects can be taken from the description of the specification, the drawings, and the claims.

Means for Solving the Problems

(13) One embodiment of the present invention is a method for forming a positive electrode active material, in which a first container that includes a mixture of lithium oxide, fluoride, and a magnesium compound and fluoride that is outside the first container are provided in a heating furnace, and the heating furnace is heated at a temperature higher than or equal to a temperature at which the fluoride is volatilized or sublimated.

(14) Another embodiment of the present invention is a method for forming a positive electrode

active material, in which a first container that includes a mixture of lithium oxide, fluoride, and a magnesium compound and a second container that includes fluoride are provided in a heating furnace, and the heating furnace is heated at a temperature higher than or equal to a temperature at which the fluoride is volatilized or sublimated.

(15) In the above structure, the fluoride is preferably lithium fluoride (LiF).

(16) In the above structure, the heating furnace is preferably heated at higher than or equal to 740° C. and lower than or equal to 1130° C.

(17) In the above structure, the magnesium compound is preferably magnesium fluoride (MgF.sub.2).

(18) In the above structure, the heating furnace is preferably heated after an atmosphere in the heating furnace is replaced with oxygen.

Effect of the Invention

(19) According to one embodiment of the present invention, a method for forming a positive electrode active material can be provided. According to another embodiment of the present invention, a novel positive electrode active material particle can be provided. According to another embodiment of the present invention, a novel power storage device can be provided.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a diagram illustrating an example of a method for forming a positive electrode active material.

(2) FIG. 2 is a diagram illustrating a DSC measurement result of a mixture of LiF and MgF.sub.2.

(3) FIG. 3 is a diagram illustrating a method for forming a positive electrode active material of one embodiment of the present invention.

(4) FIG. 4A and FIG. 4B are diagrams illustrating a method for forming a positive electrode active material of one embodiment of the present invention.

(5) FIG. 5A and FIG. 5B are diagrams illustrating a method for forming a positive electrode active material of one embodiment of the present invention.

(6) FIG. 6 is a diagram illustrating an example of a method for forming a positive electrode active material.

(7) FIG. 7 is a diagram illustrating an example of a method for forming a positive electrode active material.

(8) FIG. 8 is a diagram illustrating an example of a method for forming a positive electrode active material.

(9) FIG. 9 is a diagram illustrating crystal structures and magnetism of a positive electrode active material.

(10) FIG. 10 is a diagram illustrating crystal structures and magnetism of a positive electrode active material of a conventional example.

(11) FIG. 11A and FIG. 11B are cross-sectional views of an active material layer containing a graphene compound as a conductive additive.

(12) FIG. 12A and FIG. 12B are perspective views illustrating a coin-type secondary battery.

(13) FIG. 13A is a perspective view illustrating a cylindrical secondary battery, FIG. 13B is an exploded perspective view, FIG. 13C is a perspective view of cylindrical secondary batteries, and FIG. 13D is a top view illustrating cylindrical secondary batteries.

(14) FIG. 14A and FIG. 14B are diagrams illustrating an example of a secondary battery.

(15) FIG. 15A, FIG. 15B, FIG. 15C, and FIG. 15D are perspective views illustrating examples of a secondary battery.

(16) FIG. 16A and FIG. 16B are perspective views illustrating an example of a secondary battery.

- (17) FIG. 17A and FIG. 17B are perspective views illustrating an example of a secondary battery.
- (18) FIG. 18 is a perspective view illustrating an example of a secondary battery.
- (19) FIG. 19A, FIG. 19B, and FIG. 19C are perspective views illustrating a laminated secondary battery.
- (20) FIG. 20A is a top view illustrating a laminated secondary battery. FIG. 20B is a cross-sectional view illustrating a laminated secondary battery.
- (21) FIG. 21 is an external view of a secondary battery.
- (22) FIG. 22 is an external view of a secondary battery.
- (23) FIG. 23A, FIG. 23B, and FIG. 23C are diagrams illustrating a method for forming a secondary battery.
- (24) FIG. 24A is a top view of a bendable secondary battery, and FIG. 24B, FIG. 24C, FIG. 24D, and
- (25) FIG. 24E are cross-sectional views illustrating the secondary battery.
- (26) FIG. 25A and FIG. 25B are perspective views illustrating a bendable secondary battery.
- (27) FIG. 26A and FIG. 26B are perspective views illustrating an example of an electronic device, FIG. 26C is a perspective view of a secondary battery, FIG. 26D is a diagram illustrating an example of an electronic device, FIG. 26E is a perspective view of a secondary battery, and FIG. 26F and FIG. 26G are diagrams illustrating examples of electronic devices.
- (28) FIG. 27A and FIG. 27B are top views illustrating an example of an electronic device, and FIG. 27C is a block diagram.
- (29) FIG. 28 is a diagram illustrating examples of electronic devices.
- (30) FIG. 29A is a perspective view of a vehicle, FIG. 29B is a perspective view illustrating charging of a vehicle, and FIG. 29C is a perspective view illustrating an electric motorcycle.
- (31) FIG. 30A and FIG. 30B are photographs of an alumina crucible used in annealing.
- (32) FIG. 31 is a diagram illustrating cycle performance of Example.

MODE FOR CARRYING OUT THE INVENTION

(33) Embodiments of the present invention are described in detail with reference to the drawings. Note that the present invention is not limited to the following description, and it is readily understood by those skilled in the art that modes and details of the present invention can be modified in various ways. In addition, the present invention should not be construed as being limited to the description of embodiments below.

(34) In the crystallography, a bar is placed over a number in the expression of crystal planes and orientations; however, in this specification and the like, crystal planes and orientations are expressed by placing – (a minus sign) at the front of a number because of expression limitations. Furthermore, an individual direction which shows an orientation in a crystal is denoted by “[]”, a set direction which shows all of the equivalent orientations is denoted by “< >”, an individual plane which shows a crystal plane is denoted by “()”, and a set plane having equivalent symmetry is denoted by “{ }”.

(35) In this specification, an atmosphere including fluoride is an atmosphere of a mixed gas including fluoride as at least one of the constituting components or an atmosphere under a condition of the mixed gas.

Embodiment 1

(36) An example of a method for forming a lithium composite oxide $\text{LiMO}_{0.5}\text{O}_2$ (M is two or more kinds of metals including Co, and the substitution positions of the metals are not particularly limited) is described with reference to FIG. 1. A positive electrode active material containing Mg as a metal element contained in $\text{LiMO}_{0.5}\text{O}_2$ other than Co is described below as an example.

(37) First, a halogen source is prepared as a material of a mixture 902. As the halogen source, chloride, bromide, and iodide can be used, and fluoride is particularly preferable. In this embodiment, LiF, which is a fluorine source, is prepared as the halogen source. LiF is preferable because it has a cation common with $\text{LiCoO}_{0.5}\text{O}_2$. LiF can be used as both a lithium source and

the fluorine source. LiF, which has a relatively low melting point of 848° C., is preferable because it is easily melted in an annealing process described later. Similarly, MgF.sub.2, which can be used also as a fluorine source, is preferable as a magnesium source used for LiMO.sub.2. Note that LiCl can also be used as the halogen source, and MgCl.sub.2 can also be used as the magnesium source. Note that as a combination of the halogen source and the magnesium source, a combination having a eutectic point is preferable because a decrease in melting point, which is described later, can be utilized. Furthermore, the halogen source that can be used for one embodiment of the present invention is not limited to LiF or LiCl. Moreover, the magnesium source that can be used for one embodiment of the present invention is not limited to MgF.sub.2 or MgCl.sub.2.

(38) In this specification, the eutectic point refers to a point in a solid-liquid phase curve of two components at which the two components do not form a solid solution but completely melt and mix in the liquid state. For example, when two components of metal elements A and B are fused, in the case where A and B do not form a solid solution and form solid phases separately or form molecular compounds, and A and B are completely melted together in a liquid phase, a mixture of A and B has a melting point lower than the melting point of A or B alone, and a mixture having a certain concentration ratio of A to B has the lowest melting point. This temperature is also referred to as a eutectic point, and this mixture is also referred to as a eutectic mixture. The above description applies not only to two components but also to three, four, five, or more components.

(39) In this embodiment, LiF, which is a fluorine source, is prepared as the halogen source, and MgF.sub.2 is prepared as the fluorine source and the magnesium source (Step S11 in FIG. 1). The molar ratio of LiF to MgF.sub.2 is preferably LiF:MgF.sub.2=u:1 ($0 \leq u \leq 1.9$), further preferably LiF:MgF.sub.2=u:1 ($0.1 \leq u \leq 0.5$), still further preferably LiF:MgF.sub.2=u:1 ($u = \text{the vicinity of } 0.33$).

(40) In addition, in the case where the following mixing and grinding steps are performed by a wet process, a solvent is prepared. As the solvent, ketone such as acetone; alcohol such as ethanol or isopropanol; ether; dioxane; acetonitrile; N-methyl-2-pyrrolidone (NMP); or the like can be used. An aprotic solvent that hardly reacts with lithium is further preferably used. In this embodiment, acetone is used (see Step S11 in FIG. 1).

(41) Next, the materials of the mixture **902** are mixed and ground (Step S12 in FIG. 1). Although the mixing can be performed by a dry process or a wet process, the wet process is preferable because the materials can be ground to the smaller size. For example, a ball mill, a bead mill, or the like can be used for the mixing. When the ball mill is used, a zirconia ball is preferably used as media, for example. The mixing and grinding steps are preferably performed sufficiently to pulverize the mixture **902**.

(42) The materials mixed and ground in the above are collected (Step S13 in FIG. 1), whereby the mixture **902** is obtained (Step S14 in FIG. 1).

(43) For example, the mixture **902** preferably has an average particle diameter (D50) of greater than or equal to 600 nm and less than or equal to 20 μm , further preferably greater than or equal to 1 μm and less than or equal to 10 μm . When mixed with a composite oxide containing lithium such as lithium cobalt oxide, a transition metal, and oxygen in the later step, the mixture **902** pulverized to such a small size is easily attached to surfaces of composite oxide particles uniformly. The mixture **902** is preferably attached to the surfaces of the composite oxide particles uniformly because both halogen and magnesium are easily distributed to the surface portion of the composite oxide particles after heating. When there is a region containing neither halogen nor magnesium in the surface portion, the positive electrode active material might be less likely to have a pseudo-spinel crystal structure, which is described later, in the charged state.

(44) <Step S25>

(45) Next, a lithium source is prepared as shown in Step S25. A composite oxide which is synthesized in advance and contains lithium, a transition metal, and oxygen is used as Step S25.

(46) In the case where the composite oxide containing lithium, the transition metal, and oxygen that

is synthesized in advance is used, a composite oxide with few impurities is preferably used. In this specification and the like, lithium, cobalt, nickel, manganese, aluminum, and oxygen are the main components of the composite oxide containing lithium, the transition metal, and oxygen and the positive electrode active material, and elements other than the main components are regarded as impurities. For example, when analyzed with a glow discharge mass spectroscopy method (GD-MS), the total impurity concentration is preferably less than or equal to 10,000 ppm wt, further preferably less than or equal to 5,000 ppm wt. In particular, the total impurity concentration of transition metals such as titanium and arsenic is preferably less than or equal to 3,000 ppm wt, further preferably less than or equal to 1,500 ppm wt.

(47) For example, as lithium cobalt oxide synthesized in advance, a lithium cobalt oxide particle (product name: CELLSEED C-10N) formed by NIPPON CHEMICAL INDUSTRIAL CO., LTD. can be used. This is lithium cobalt oxide in which the average particle diameter (D50) is approximately 12 μm , and in the impurity analysis by a glow discharge mass spectroscopy method, the magnesium concentration and the fluorine concentration are less than or equal to 50 ppm wt, the calcium concentration, the aluminum concentration, and the silicon concentration are less than or equal to 100 ppm wt, the nickel concentration is less than or equal to 150 ppm wt, the sulfur concentration is less than or equal to 500 ppm wt, the arsenic concentration is less than or equal to 1100 ppm wt, and the concentrations of elements other than lithium, cobalt, and oxygen are less than or equal to 150 ppm wt.

(48) The composite oxide containing lithium, the transition metal, and oxygen in Step S25 preferably has a layered rock-salt crystal structure with few defects and distortions. Therefore, the composite oxide is preferably a composite oxide with few impurities. In the case where the composite oxide containing lithium, the transition metal, and oxygen includes a large number of impurities, the crystal structure is highly likely to have a large number of defects or distortions.

(49) Next, the mixture **902** and the composite oxide containing lithium, the transition metal, and oxygen are mixed (Step S31 in FIG. 1). The atomic ratio of the transition metal TM in the composite oxide containing lithium, the transition metal, and oxygen to magnesium MgMix1 contained in the mixture **902** is preferably $\text{TM:MgMix1}=1:\nu$ ($0.005 \leq \nu \leq 0.05$), further preferably $\text{TM:Mg.sub.Mix1}=1:\nu$ ($0.007 \leq \nu \leq 0.04$), still further preferably approximately $\text{TM:Mg.sub.Mix1}=1:0.02$.

(50) The condition of the mixing in Step S31 is preferably milder than that of the mixing in Step S12 not to damage the particles of the composite oxide. For example, a condition with a lower rotation frequency or shorter time than the mixing in Step S12 is preferable. In addition, it can be said that the dry process has a milder condition than the wet process. For example, a ball mill, a bead mill, or the like can be used for the mixing. When the ball mill is used, a zirconia ball is preferably used as media, for example.

(51) The materials mixed in the above manner are collected (Step S32 in FIG. 1), whereby a mixture **903** is obtained (Step S33 in FIG. 1).

(52) Next, the mixture **903** is heated (Step S34 in FIG. 1). This step is referred to as annealing in some cases. LiMO.sub.2 is formed by the annealing. Thus, the conditions of performing Step S34, such as temperature, time, an atmosphere, and weight of the mixture **903** on which the annealing is performed, are important. In this specification, annealing includes, in meaning, a case where the mixture **903** is heated and a case where a heating furnace in which at least the mixture **903** is provided is heated.

(53) In the case where the conditions of S34 are not appropriate, a positive electrode active material having excellent characteristics cannot be obtained in some cases.

(54) Here, the present inventors have found that annealing performed in an atmosphere including fluoride included in the mixture **903** (in the case of this embodiment, LiF) enables a positive electrode active material having excellent characteristics to be formed.

(55) [Effects of Annealing in Atmosphere Including Fluoride]

(56) The annealing temperature is preferably higher than or equal to a temperature at which the mixture **902** is melted. When the mixture **903** is annealed, the mixture **902** is presumed to be melted. For example, the mixture of MgF.sub.2 (melting point: 1263° C.) and LiF (melting point: 848° C.) is considered to be melted and distributed to surface portions of the composite oxide particles. It is considered that when MgF.sub.2 is melted, a reaction with LiCoO.sub.2 is promoted, so that LiMO.sub.2 is formed. Thus, a combination of the fluoride and the magnesium source preferably forms a eutectic mixture.

(57) The annealing temperature is further preferably higher than or equal to a temperature at which the mixture **903** is melted. When fluoride (e.g., LiF), a magnesium source (e.g., MgF.sub.2), and lithium oxide (e.g., LiCoO.sub.2) form a shared mixture, formation of LiMO.sub.2 is probably promoted.

(58) The annealing temperature needs to be lower than or equal to a decomposition temperature of LiCoO.sub.2 (1130° C.). Thus, the heating is preferably performed at higher than or equal to the eutectic point of the fluoride and the magnesium source and lower than or equal to 1130° C.

(59) Note that the eutectic point of LiF and MgF.sub.2 is around 735° C., which is described later. Furthermore, an endothermic peak of LiF, MgF.sub.2, and LiCoO.sub.2 is observed at around 820° C. in differential scanning calorimetry (DSC measurement). Thus, the annealing temperature is preferably higher than or equal to 735° C., further preferably higher than or equal to 820° C. Since the decomposition temperature of LiCoO.sub.2 is 1130° C., decomposition of a slight amount of LiCoO.sub.2 is concerned at a temperature close to the decomposition temperature. Thus, the annealing temperature is preferably lower than or equal to 1130° C., further preferably lower than or equal to 1000° C.

(60) Accordingly, the annealing temperature is preferably higher than or equal to 735° C. and lower than or equal to 1130° C., further preferably higher than or equal to 735° C. and lower than or equal to 1000° C. Moreover, the annealing temperature is preferably higher than or equal to 820° C. and lower than or equal to 1130° C., further preferably higher than or equal to 820° C. and lower than or equal to 1000° C.

(61) Here, the DSC measurement of the mixture of LiF and MgF.sub.2 is described.

(62) As the measurement device, Thermo plus EV02 produced by Rigaku Corporation is used. The measurement is performed in a temperature range from 25° C. to 1000° C. at a temperature rising rate of 20° C./min.

(63) FIG. 2 shows the DSC measurement result of the mixture of LiF and MgF.sub.2 (LiF/MgF.sub.2=0.33 mol %). As shown in FIG. 2, the endothermic peak is observed at around 735° C. Thus, the mixture of LiF and MgF.sub.2 has a eutectic point of around 735° C.

(64) In this embodiment, LiF, which is fluoride, is considered to function as flux. Thus, it is presumed that when LiF is volatilized and the amount of LiF in the mixture **903** is decreased, MgF.sub.2 is less likely to be melted so that formation of LiMO.sub.2 is inhibited. Therefore, heating needs to be performed while volatilization of LiF is inhibited.

(65) Thus, when the mixture **903** is heated in an atmosphere including LiF, that is, the mixture **903** is heated in a state where the partial pressure of LiF in the heating furnace is high, volatilization of LiF in the mixture **903** can be inhibited and formation of LiMO.sub.2 can progress efficiently. Accordingly, a positive electrode active material having excellent characteristics can be formed.

(66) Here, a weight loss percentage in the case where the mixture of LiF and MgF.sub.2 (LiF/MgF.sub.2=0.33 mol %) is heated at a predetermined temperature can be found out by an experiment. The experiment method is as follows: the mixture of LiF and MgF.sub.2 is heated to a predetermined temperature at a temperature rising rate of 200° C./h, and the predetermined temperature is held for 10 hours. After that, the temperature is lowered for longer than or equal to 10 hours. Moreover, the heating is performed while oxygen flows at a flow rate of 5.0 L/min. Table 1 shows the results of the weight loss percentage measurement. Note that the weight loss percentages (%) in Table 1 are the results calculated by the following formula: a difference in

weight of the mixture between before and after the heating/weight of the mixture before the heating×100.

(67) TABLE-US-00001 TABLE 1 Heating Weight loss temperature percentage (° C.) (%) 600 1 700 2 800 8 900 26

(68) As shown in Table 1, the weight loss of the mixture of LiF and MgF.sub.2 is observed at least at 700° C. Thus, it is found that components of LiF and MgF.sub.2 are volatilized from a reaction system at a temperature of at least 700° C. or higher.

(69) [Annealing 1 in Atmosphere Including Fluoride]

(70) An example of a method for performing annealing while the atmosphere in a heating furnace is made into an atmosphere including fluoride is described with reference to FIG. 3.

(71) A heating furnace in this specification is equipment used for performing heat treatment (annealing) on a substance or a mixture and includes a heater and an inner wall that can withstand an atmosphere including fluoride and at least 600° C. Furthermore, the heating furnace may be provided with a pump having a function of reducing and/or increasing pressure in the heating furnace.

(72) A heating furnace **100** includes a space **102** in the heating furnace, a hot plate **104**, a heater **106**, a heat insulator **108**, a gas supply line **110**, a gate valve **112**, and a gas exhaust line **114**. As a method for annealing the mixture **903** in an atmosphere including fluoride, a method in which a container **116** including the mixture **903** is provided in the space **102** in the heating furnace, a gas of fluoride is introduced from the gas supply line **110** into the space **102** in the heating furnace, and annealing is performed is given. In the case where fluoride having a corrosion property is used, the hot plate **104**, the gas supply line **110**, the gate valve **112**, the gas exhaust line **114**, the inner wall of the heating furnace, and the container **116** are preferably formed or processed using a material which is not damaged by fluoride and has high heat resistance. As the material, a ceramic material is given, and aluminum oxide can be used, for example. Note that in the case where LiF or the like which has low reactivity is used, another material such as a metal having high heat resistance can also be used.

(73) In the case where a gas of fluoride is introduced, the gas is preferably introduced while the space **102** in the heating furnace is heated to a temperature higher than or equal to the freezing point or condensing point of the fluoride. In the case where the temperature in the space **102** in the heating furnace is low, the state of the introduced gas is changed to a liquid or solid state in some cases.

(74) The valence number of Co (cobalt) in LiMO.sub.2 formed by one embodiment of the present invention is preferably 3. The valence number of Co can be 2 or 3. Thus, to inhibit reduction of Co, it is preferable that the atmosphere in the space **102** in the heating furnace contain oxygen, the ratio of oxygen to nitrogen in the atmosphere in the space **102** in the heating furnace be higher than or equal to that in the air atmosphere, and the oxygen concentration in the atmosphere in the space **102** in the heating furnace be higher than or equal to that in the air atmosphere. Oxygen is preferably introduced through the gas supply line **110** in addition to fluoride. Note that although only one gas supply line is shown in FIG. 3, two or more gas supply lines may be provided. In that case, fluoride and oxygen may be introduced into the space **102** in the heating furnace through different lines.

(75) Note that there is no particular limitation on the order of the step of providing the container **116** including the mixture **903** and the step of adjusting the atmosphere in the space **102** in the heating furnace (introducing a fluoride gas or adjusting the oxygen concentration). That is, after the container **116** including the mixture **903** is provided, the atmosphere in the space **102** in the heating furnace may be adjusted; the order may be reversed. After the container **116** is provided in the space **102** in the heating furnace and the atmosphere in the space **102** in the heating furnace is adjusted, the heating furnace **100** is heated, that is, the space **102** in the heating furnace is heated, whereby the mixture **903** can be annealed in the atmosphere including fluoride.

(76) Alternatively, after the heating furnace **100** is heated and the atmosphere in the space **102** in the heating furnace is adjusted, the container **116** including the mixture **903** may be provided. In this case, there is no particular limitation on the order of the step of adjusting the atmosphere in the space **102** in the heating furnace and the step of heating the heating furnace **100**.

(77) Although there is no particular limitation on the way of providing the mixture **903** in the container **116**, as shown in FIG. 3, the mixture **903** is preferably provided so that the top surface of the mixture **903** is flat on the bottom surface of the container **116**, in other words, the level of the top surface of the mixture **903** becomes uniform.

(78) [Annealing 2 in Atmosphere Including Fluoride]

(79) Examples of a method for performing annealing while the atmosphere in a heating furnace is made into an atmosphere including fluoride are described with reference to FIG. 4A and FIG. 4B. Note that in FIG. 4A and FIG. 4B, a portion having a function similar to that of a portion denoted by a reference numeral shown in FIG. 3 is represented by the same hatch pattern and the reference numeral is omitted in some cases. In addition, common reference numerals are used for portions having similar functions, and a detailed description thereof is omitted in some cases.

(80) A heating furnace **120** illustrated in FIG. 4A and FIG. 4B includes the space **102** in the heating furnace, the hot plate **104**, the heater **106**, and the heat insulator **108**. As a method for annealing the mixture **903** in an atmosphere including fluoride, a method which is shown in FIG. 4A and in which the container **116** including the mixture **903** is provided in the space **102** in the heating furnace, a container **122** including fluoride **906** that is used for the mixture **903** is provided, and the container **116** and the container **122** are heated at the same time is given. When the fluoride **906** in the container **122** is volatilized or sublimated, the atmosphere in the heating furnace can be made into an atmosphere including fluoride. Note that the fluoride **906** may be provided in the space **102** in the heating furnace without the container **122**. The space **102** in the heating furnace needs to be heated to a temperature higher than or equal to a temperature at which the fluoride **906** is volatilized or sublimated so that the atmosphere in the space **102** in the heating furnace includes the fluoride **906**.

(81) Note that the fluoride used for the mixture **903** and the fluoride **906** included in the container **122** contain the same substance, and the purity may be different or the same. For example, in the case where LiF is used as the fluoride of the mixture **903**, the purity of LiF used for the mixture **903** may be different from or the same as that of LiF included in the container **122**. A mixture of LiF and another substance may be used as the fluoride **906** as long as reaction does not occur.

(82) Note that there is no particular limitation on the order of providing the container **116** including the mixture **903** and the container **122** including the fluoride **906** in the heating furnace **120**. After the container **116** is provided, the container **122** may be provided; the order may be reversed. Alternatively, the container **116** and the container **122** may be provided at the same time.

(83) Moreover, as described above, to inhibit reduction of Co, annealing is preferably performed at an oxygen concentration higher than or equal to that in the atmospheric pressure. Thus, annealing is preferably performed after the oxygen concentration in the space **102** in the heating furnace is increased to higher than or equal to that in the atmospheric pressure.

(84) Here, there is no particular limitation on the order of the step of providing the container **116** including the mixture **903** in the heating furnace **120**, the step of providing the container **122** including the fluoride **906** in the heating furnace **120**, and the step of adjusting the oxygen concentration in the space **102** in the heating furnace. That is, after the oxygen concentration in the space **102** in the heating furnace is adjusted, the container **116** and the container **122** may be provided in the heating furnace **120**; the order may be reversed. Alternatively, after the container **116** is provided in the heating furnace **120**, the oxygen concentration in the space **102** in the heating furnace may be adjusted and the container **122** may be provided in the heating furnace **120**. Alternatively, after the container **122** is provided in the heating furnace **120**, the oxygen concentration in the space **102** in the heating furnace may be adjusted and the container **116** may be

provided in the heating furnace **120**. Heating the heating furnace **120** after these steps enables annealing of the mixture **903** in an atmosphere including fluoride. Note that among these steps, the step of heating the heating furnace **120** is preferably performed last. When the heating is performed last, the fluoride **906** and the mixture **903** can be inhibited from being heated rapidly; thus, uniform chemical reaction or state change can occur and an undesirable phenomenon such as bumping can be inhibited.

(85) Alternatively, after the step of heating the heating furnace **120**, the step of adjusting the oxygen concentration in the space **102** in the heating furnace, and the step of providing the container **122** including the fluoride **906** in the heating furnace **120** are performed, the container **116** including the mixture **903** may be provided in the heating furnace **120**. When the container **122** is heated at a temperature higher than or equal to a temperature at which the fluoride **906** is volatilized or a sublimation point, the atmosphere in the space **102** in the heating furnace can be an atmosphere including the fluoride **906**. Thus, when the container **116** including the mixture **903** is provided in the heating furnace **120** after the step of adjusting the atmosphere in the space **102** in the heating furnace (making the atmosphere include the fluoride **906** and have adjusted oxygen concentration) is performed, the mixture **903** can be annealed in the atmosphere including fluoride.

(86) In the case where the container **116** including the mixture **903** is provided in the heating furnace **120** after the step of adjusting the atmosphere in the space **102** in the heating furnace is performed, there is no particular limitation on the order of the step of heating the heating furnace **120**, the step of adjusting the oxygen concentration in the space **102** in the heating furnace, and the step of providing the container **122** including the fluoride **906** in the heating furnace **120**. For example, after the heating furnace **120** is heated, the oxygen concentration in the space **102** in the heating furnace may be adjusted and the container **122** may be provided in the heating furnace **120**, or after the container **122** is provided in the heating furnace **120**, the oxygen concentration in the space **102** in the heating furnace may be adjusted and the heating may be performed.

(87) As shown in FIG. **4B**, the mixture **903** may be provided in one space of a container **124** provided with a divider **126**, and the fluoride **906** may be provided in the other space. With the structure, the mixture **903** and the fluoride **906** can be provided in the heating furnace **120** at the same time. Furthermore, with the structure, the atmosphere in the space **102** in the heating furnace can include fluoride without mixing of the mixture **903** and the fluoride **906** when they are melted.

(88) Note that as described above, the fluoride used for the mixture **903** and the fluoride **906** contain the same substance, and the purity may be different or the same. For example, in the case where LiF is used as the fluoride of the mixture **903**, the purity of LiF used for the mixture **903** may be different from or the same as that of LiF used as the fluoride **906**.

(89) The annealing is preferably performed at an appropriate temperature for an appropriate time. The appropriate temperature and time depend on the conditions such as the particle size and the composition of the composite oxide containing lithium, the transition metal, and oxygen in Step **S25**. In the case where the particle size is small, the annealing is preferably performed at a lower temperature or for a shorter time than the case where the particle size is large, in some cases.

(90) For example, in the case where the average particle diameter (D50) of particles in Step **S25** is approximately 12 μm , the annealing time is preferably 3 hours or longer, further preferably 10 hours or longer.

(91) In contrast, in the case where the average particle diameter (D50) of particles in Step **S25** is approximately 5 μm , the annealing time is preferably longer than or equal to 1 hour and shorter than or equal to 10 hours, further preferably approximately 2 hours, for example.

(92) The temperature decreasing time after the annealing is, for example, preferably longer than or equal to 10 hours and shorter than or equal to 50 hours.

(93) The materials annealed in the above manner are collected (Step **S35** in FIG. **1**), whereby a positive electrode active material **904** is obtained (Step **S36** in FIG. **1**).

(94) FIG. **5** illustrates examples of a heating furnace. Note that in FIG. **5**, a portion having a

function similar to that of a portion denoted by a reference numeral in FIG. 3 is represented by the same hatch pattern and a reference numeral is omitted in some cases. In addition, common reference numerals are used for portions having similar functions, and a detailed description thereof is omitted in some cases.

(95) <Structure of Heating Furnace>

(96) There is no particular limitation on the heating furnace used for one embodiment of the present invention, and a variety of heating furnaces such as a batch-type or sequential heating furnace can be used. Examples thereof are illustrated in FIG. 5A and FIG. 5B.

(97) A heating furnace **130** illustrated in FIG. 5A is an example of a sequential heating furnace. The heating furnace **130** includes a conveyor belt **132**. Containers **134** including the mixture **903** are provided over the conveyor belt **132**, and processing is performed in the heating furnace **130**, so that the annealing can be performed sequentially. Adjusting the moving speed of the conveyor belt enables adjustment of the annealing time. Furthermore, when the fluoride **906** is provided in one of the containers **134** and is annealed at the same time as the mixture **903**, the atmosphere in the space **102** in the heating furnace can include fluoride. The mixture **903** is annealed in the heating furnace **130**, so that the positive electrode active material **904** can be obtained.

(98) A heating furnace **140** illustrated in FIG. 5B is an example of a rotational heating furnace. The heating furnace **140** includes a material input port **142**, an atmosphere control portion **144**, and a collecting portion **146**. The mixture **903** is input from the material input port **142** to the space **102** in the heating furnace. The hot plate **104** includes a rotating mechanism, and the hot plate **104** is tilted to the collecting portion **146**. With the structure, the annealing can be performed with the mixture **903** flowing. Adjustment of the tilt or rotating speed of the hot plate **104** enables adjustment of the annealing time. The annealed mixture **903** is collected in the collecting portion **146**, whereby the positive electrode active material **904** can be obtained.

(99) With the atmosphere control portion **144**, the atmosphere in the space **102** in the heating furnace can be an atmosphere including fluoride. As a method for making the atmosphere include fluoride, as described above, a method for introducing a fluoride gas and a method for sublimating or volatilizing fluoride can be given.

Embodiment 2

(100) An example of a method for forming LiMO.sub.2 is described. A forming method in the case where a plurality of metal elements are further used as the metal element contained in LiMO.sub.2 other than Co is described below with reference to FIG. 6.

(101) <<Forming Method 2 of Positive Electrode Active Material>>

(102) FIG. 6 illustrates an example of forming steps of a composite oxide LiMO.sub.2 containing Mg, Ni, and Al other than Co. This forming method is as follows: metal element sources other than Li and Co are separately mixed and subjected to grinding treatment, and after that, each metal element source subjected to the grinding treatment is mixed with lithium cobalt oxide and annealed. S11 to S36 are similar to the steps described in Embodiment 1 and FIG. 1. That is, a mixture **903-2** is preferably annealed in an atmosphere including LiF in Step S34. Through the forming steps illustrated in FIG. 6, a positive electrode active material **904-2** can be obtained.

(103) <Step S15, Step S16, and Step S17>

(104) Nickel hydroxide (Ni(OH).sub.2) that is pulverized to be mixed in Step S31 is prepared. On the pulverized nickel hydroxide, Step S15 for mixing nickel hydroxide and acetone and Step S16 for collecting the mixture are performed in advance. Through Step S16, the pulverized nickel hydroxide is obtained (Step S17).

(105) <Step S18, Step S19, and Step S20>

(106) Aluminum hydroxide (Al(OH).sub.3) that is pulverized to be mixed in Step S31 is prepared. On the pulverized aluminum hydroxide, Step S18 for mixing aluminum hydroxide and acetone and Step S19 for collecting the mixture are performed in advance. Through Step S19, the pulverized aluminum hydroxide is obtained (Step S20).

(107) Although nickel hydroxide is used as the nickel (Ni) source and aluminum hydroxide is used as the aluminum (Al) source in Step S15 to S20 described above, the nickel source and the aluminum source are not limited to them. An oxide or a halide containing each element can also be used.

(108) <<Forming Method 3 of Positive Electrode Active Material>>

(109) FIG. 7 illustrates an example of steps of forming a composite oxide LiMO.sub.2 containing Mg, Ni, and Al other than Co. This forming method is as follows: metal element sources other than Li and Co are mixed at the same time and subjected to grinding treatment, and after that, the mixture is mixed with lithium cobalt oxide and annealed. S31 to S35 are similar to the steps described in Embodiment 1 and FIG. 1. That is, a mixture 903-3 is preferably annealed in an atmosphere including LiF in Step S34. Through the forming steps illustrated in FIG. 7, a positive electrode active material 904-3 can be obtained.

(110) <Step S22 to Step S24>

(111) As in Step S15 to Step S17 and Step S18 to Step S20 described above, MgF.sub.2 , Ni(OH).sub.2 , and Al(OH).sub.3 which are pulverized are prepared. On the pulverized aluminum hydroxide, Step S22 for mixing aluminum hydroxide and acetone and Step S23 for collecting the mixture are performed in advance. Through Step S22, a pulverized mixture 902-3 is obtained (Step S24).

(112) <<Forming Method 4 of Positive Electrode Active Material>>

(113) FIG. 8 illustrates an example of steps of forming a composite oxide LiMO.sub.2 containing Mg, Ni, and Al other than Co. This forming method is as follows: a composite oxide which contains Mg and is expressed by LiMO.sub.2 is formed, and then a Ni source and an Al source are added, so that a composite oxide containing Mg, Ni, and Al is formed. S11 to S14 and S31 to S36 are similar to the steps described in Embodiment 1 and FIG. 1. That is, the mixture 903 is preferably annealed in an atmosphere including LiF in Step S34. Step S15 to Step S17 are similar to the steps described with reference to FIG. 6. Through the forming steps illustrated in FIG. 8, a positive electrode active material 904-4 can be obtained.

(114) Next, as shown in Step S50, the positive electrode active material 904 and pulverized nickel hydroxide are mixed. Then, the mixed materials are collected (Step S51). For the pulverized nickel hydroxide, Step S15 for mixing nickel hydroxide and acetone and Step S16 for collecting the mixture are performed in advance. Through Step S16, the pulverized nickel hydroxide is obtained (Step S17).

(115) The materials mixed in Step S50 are collected in Step S51, whereby a mixture 908 is obtained (Step S52 in FIG. 8).

(116) Next, through Step S53 to Step S55, Al is added. For the addition of Al, a liquid phase method such as a sol-gel method, a solid phase method, a sputtering method, an evaporation method, a CVD (chemical vapor deposition) method, a PLD (pulsed laser deposition) method, and the like can be used.

(117) As shown in FIG. 8, a metal source is first prepared in Step S52. In the case of employing a sol-gel method, a solvent used for the sol-gel method is prepared. As the Al source, Al alkoxide, Al hydroxide, Al oxide, or the like can be used. The concentration of aluminum in the metal source is 0.001 times or more and 0.02 times or less as high as that of cobalt with the number of cobalt atoms in the lithium cobalt oxide regarded as 1.

(118) Here, an example of employing a sol-gel method using aluminum isopropoxide as the metal source and 2-propanol as the solvent is shown.

(119) Next, aluminum alkoxide is dissolved in 2-propanol, and furthermore, a mixture 905 is mixed (Step S53 in FIG. 8).

(120) The necessary amount of metal alkoxide depends on the particle size of lithium cobalt oxide. For example, when aluminum isopropoxide is used and the particle diameter (D50) of the lithium cobalt oxide is approximately 20 μm , the aluminum isopropoxide is preferably added so that the

concentration of aluminum in the aluminum isopropoxide is 0.001 times or more and 0.02 times or less as high as that of cobalt with the number of cobalt atoms in the lithium cobalt oxide regarded as 1.

(121) Next, a mixed solution of the alcohol solution of metal alkoxide and the lithium cobalt oxide particles is stirred under an atmosphere including moisture. The stirring can be performed with a magnetic stirrer, for example. The stirring time is not limited as long as water and metal alkoxide in the atmosphere cause hydrolysis and polycondensation reaction. For example, the stirring can be performed at 25° C. and a humidity of 90% RH (Relative Humidity) for 4 hours. Alternatively, the stirring may be performed under an atmosphere where the humidity and temperature are not adjusted, for example, an air atmosphere in a fume hood. In such a case, the stirring time is preferably set longer and can be 12 hours or longer at room temperature, for example.

(122) Reaction between moisture and metal alkoxide in the atmosphere enables a sol-gel reaction to proceed more slowly as compared with the case where liquid water is added. Alternatively, reaction between metal alkoxide and water at room temperature enables a sol-gel reaction to proceed more slowly as compared with the case where heating is performed at a temperature higher than the boiling point of alcohol serving as a solvent, for example. A sol-gel reaction that proceeds slowly enables formation of a high-quality coating layer with a uniform thickness.

(123) After the above process, the precipitate is collected from the mixed solution (Step S54 in FIG. 8). As the collection method, filtration, centrifugation, evaporation to dryness, and the like can be used. The precipitate can be washed with alcohol that is the same as the solvent in which metal alkoxide is dissolved. Note that in the case of employing evaporation to dryness, the solvent and the precipitate are not necessarily separated in this step; for example, the precipitate is collected in the subsequent drying step (Step S54).

(124) Next, the collected residue is dried, so that a mixture **909** is obtained (Step S55 in FIG. 8). In the drying step, vacuum or ventilation drying can be performed at 80° C. for longer than or equal to 1 hour and shorter than or equal to 4 hours, for example.

(125) Then, the obtained mixture is heated (Step S56 in FIG. 8).

(126) As for the heating time, the time for keeping the heating temperature within a predetermined range is preferably longer than or equal to 1 hour and shorter than or equal to 80 hours.

(127) The heating temperature is lower than 1000° C., preferably higher than or equal to 700° C. and lower than or equal to 950° C., further preferably approximately 850° C.

(128) The heating is preferably performed in an oxygen-containing atmosphere.

(129) In this embodiment, the heating temperature is 850° C. and kept for 2 hours, the temperature rising rate is 200° C./h, and the flow rate of oxygen is 10 L/min.

(130) The heating temperature in Step S56 is preferably lower than the heating temperature in Step S34.

(131) <Step S57 and Step S58>

(132) Next, cooled particles are collected (Step S57 in FIG. 8). Moreover, the particles are preferably made to pass through a sieve. Through the above steps, the positive electrode active material **904-4** can be formed (Step S58 in FIG. 8).

Embodiment 3

(133) In this embodiment, an example of a structure of a positive electrode active material formed by the forming method of one embodiment of the present invention is described.

(134) [Structure of Positive Electrode Active Material]

(135) A material with a layered rock-salt crystal structure, such as lithium cobalt oxide (LiCoO₂), is known to have a high discharge capacity and excel as a positive electrode active material of a secondary battery. As an example of the material with a layered rock-salt crystal structure, a composite oxide represented by LiMO₂ is given. As an example of the element M, one or more elements selected from Co and Ni can be given. As another example of the element M, in addition to one or more elements selected from Co and Ni, one or more elements selected from

Al and Mg can be given.

(136) It is known that the Jahn-Teller effect in a transition metal compound varies in degree according to the number of electrons in the d orbital of the transition metal.

(137) In a compound containing nickel, distortion is likely to be caused because of the Jahn-Teller effect in some cases. Accordingly, when high-voltage charge and discharge are performed on $\text{LiNiO}_{0.2}$, the crystal structure might be disordered because of the distortion. The influence of the Jahn-Teller effect is suggested to be small in $\text{LiCoO}_{0.2}$; hence, $\text{LiCoO}_{0.2}$ is preferable because the resistance to high-voltage charge and discharge is higher in some cases.

(138) Positive electrode active materials are described with reference to FIG. 9 and FIG. 10. In FIG. 9 and FIG. 10, the case where cobalt is used as a transition metal contained in the positive electrode active material is described.

(139) In the positive electrode active material formed by one embodiment of the present invention, the difference in the positions of $\text{CoO}_{0.2}$ layers can be small in repeated charge and discharge at high voltage. Furthermore, the change in the volume can be small. Thus, the compound can have excellent cycle performance. In addition, the compound can have a stable crystal structure in a high-voltage charged state. Thus, in the compound, a short circuit is less likely to occur while the high-voltage charged state is maintained. This is preferable because the safety is further improved. In particular, a compound represented by a chemical formula $\text{Li}_{1-x-y}\text{Co}_{1-a-b}\text{Ni}_{x+a}\text{Mg}_{y+b}\text{O}_{0.2}$ have excellent characteristics when $0 < x+a \leq 0.015$ and $0 < y+b \leq 0.06$.

(140) The compound has a small change in the crystal structure and a small difference in volume per the same number of transition metal atoms between a sufficiently discharged state and a high-voltage charged state.

(141) FIG. 9 illustrates the crystal structures of the positive electrode active material **904** before and after being charged and discharged. The positive electrode active material **904** is a composite oxide containing lithium, cobalt, and oxygen. In addition to the above, the positive electrode active material **904** preferably contains magnesium. Furthermore, the positive electrode active material **904** preferably contains halogen such as fluorine or chlorine. The positive electrode active material **904** preferably contains aluminum and nickel.

(142) The crystal structure with a charge depth of 0 (the discharged state) in FIG. 9 is R-3m (O3), which is the same as that in FIG. 10. Meanwhile, the positive electrode active material **904** with a charge depth in a sufficiently charged state includes a crystal whose structure is different from the H1-3 type structure. This structure belongs to the space group R-3m, and is not a spinel crystal structure but a structure in which an ion of cobalt, magnesium, or the like is coordinated to six oxygen atoms and the cation arrangement has symmetry similar to that of the spinel crystal structure. This structure is thus referred to as the pseudo-spinel crystal structure in this specification and the like. Note that although the indication of lithium is omitted in the diagram of the pseudo-spinel crystal structure shown in FIG. 9 to explain the symmetry of cobalt atoms and the symmetry of oxygen atoms, a lithium of 20 atomic % or less, for example, with respect to cobalt practically exists between the $\text{CoO}_{0.2}$ layers. In addition, in both the O3-type crystal structure and the pseudo-spinel crystal structure, a slight amount of magnesium preferably exists between the $\text{CoO}_{0.2}$ layers, i.e., in lithium sites. In addition, a slight amount of halogen such as fluorine may exist in oxygen sites at random.

(143) Note that in the pseudo-spinel crystal structure, oxygen is tetraordinated to a light element such as lithium in some cases. Also in that case, the ion arrangement has symmetry similar to that of the spinel crystal structure.

(144) The pseudo-spinel crystal structure can also be regarded as a crystal structure that contains Li between layers at random but is similar to a $\text{CdCl}_{0.2}$ type crystal structure. The crystal structure similar to the $\text{CdCl}_{0.2}$ type crystal structure is close to a crystal structure of lithium nickel oxide when charged up to a charge depth of 0.94 ($\text{Li}_{0.06}\text{NiO}_{0.2}$); however, pure lithium cobalt oxide or a layered rock-salt positive electrode active material containing a large amount of cobalt is

known not to have this crystal structure generally.

(145) Anions of a layered rock-salt crystal and anions of a rock-salt crystal have cubic closest packed structures (face-centered cubic lattice structures). Anions of a pseudo-spinel crystal are also presumed to have cubic closest packed structures. When the pseudo-spinel crystal is in contact with the layered rock-salt crystal and the rock-salt crystal, there is a crystal plane at which orientations of cubic closest packed structures composed of anions are aligned. Note that a space group of the layered rock-salt crystal and the pseudo-spinel crystal is R-3m, which is different from a space group Fm-3m of a rock-salt crystal (a space group of a general rock-salt crystal) and a space group Fd-3m of a rock-salt crystal (a space group of a rock-salt crystal having the simplest symmetry); thus, the Miller index of the crystal plane satisfying the above conditions in the layered rock-salt crystal and the pseudo-spinel crystal is different from that in the rock-salt crystal. In this specification, a state where the orientations of the cubic closest packed structures composed of anions in the layered rock-salt crystal, the pseudo-spinel crystal, and the rock-salt crystal are aligned is referred to as a state where crystal orientations are substantially aligned in some cases.

(146) In the positive electrode active material **904**, a change in the crystal structure when the positive electrode active material **904** is charged with high voltage and a large amount of lithium is extracted is inhibited as compared with a positive electrode active material **100C** described later. As indicated by the dotted lines in FIG. 9, for example, there is a very little deviation in the CoO.sub.2 layers between the crystal structures.

(147) More specifically, the structure of the positive electrode active material **904** is highly stable even when a charge voltage is high. For example, at a charge voltage that makes the positive electrode active material **100C** have the H1-3 type crystal structure, for example, at a voltage of approximately 4.6 V with reference to the potential of a lithium metal, a charge voltage region where the R-3m (O3) crystal structure can be maintained exists. Moreover, in a higher charge voltage region, for example, at voltages of approximately 4.65 V to 4.7 V with reference to the potential of a lithium metal, the pseudo-spinel crystal structure can be obtained. At a much higher charge voltage, the H1-3 type structure is eventually observed in some cases. In the case where graphite, for instance, is used as a negative electrode active material in a secondary battery, when the voltage of the secondary battery is higher than or equal to 4.3 V and lower than or equal to 4.5 V, for example, a charge voltage region where the R-3m (O3) crystal structure can be maintained exists. In a higher charge voltage region, for example, at a voltage higher than or equal to 4.35 V and lower than or equal to 4.55 V with reference to the potential of a lithium metal, the pseudo-spinel crystal structure can be obtained.

(148) Thus, in the positive electrode active material **904**, the crystal structure is less likely to be disordered even when charge and discharge are repeated at high voltage.

(149) Note that in the unit cell of the pseudo-spinel crystal structure, coordinates of cobalt and oxygen can be represented by Co (0, 0, 0.5) and O (0, 0, x) within the range of $0.20 \leq x \leq 0.25$.

(150) A slight amount of magnesium existing between the CoO.sub.2 layers, i.e., in lithium sites at random, has an effect of inhibiting a deviation in the CoO.sub.2 layers. Thus, the existence of magnesium between the CoO.sub.2 layers makes it easier to obtain the pseudo-spinel crystal structure. Therefore, magnesium is preferably distributed over whole particles of a positive electrode active material **100A-1**. In addition, to distribute magnesium over whole particles, heat treatment is preferably performed in the forming process of the positive electrode active material **100A-1**.

(151) However, cation mixing occurs when the heat treatment temperature is excessively high, so that magnesium is highly likely to enter the cobalt sites. Magnesium in the cobalt sites eliminates the effect of maintaining the R-3m structure. Furthermore, when the heat treatment temperature is excessively high, adverse effects such as reduction of cobalt to have a valence of two and transpiration of lithium are concerned.

(152) In view of the above, a halogen compound such as a fluorine compound is preferably added

to lithium cobalt oxide before the heat treatment for distributing magnesium over whole particles. The addition of the halogen compound decreases the melting point of lithium cobalt oxide. The decrease in the melting point makes it easier to distribute magnesium over whole particles at a temperature at which the cation mixing is unlikely to occur. Furthermore, the existence of the fluorine compound expects to improve corrosion resistance to hydrofluoric acid generated by decomposition of an electrolyte solution.

(153) When the magnesium concentration is higher than a predetermined value, the effect of stabilizing a crystal structure becomes small in some cases. This is probably because magnesium enters the cobalt sites in addition to the lithium sites. The number of magnesium atoms in the positive electrode active material formed by one embodiment of the present invention is preferably 0.001 times or more and 0.1 times or less, further preferably more than 0.01 times and less than 0.04 times, still further preferably approximately 0.02 as large as the number of cobalt atoms. The magnesium concentration described here may be a value obtained by element analysis on the entire particles of the positive electrode active material using ICP-MS or the like, or may be a value based on the ratio of the raw materials mixed in the forming process of the positive electrode active material, for example.

(154) The number of nickel atoms in the positive electrode active material **904** is preferably 7.5% or lower, preferably 0.05% or higher and 4% or lower, further preferably 0.1% or higher and 2% or lower of the number of cobalt atoms. The nickel concentration described here may be a value obtained by element analysis on the entire particle of the positive electrode active material using ICP-MS or the like, or may be a value based on the ratio of the raw materials mixed in the forming process of the positive electrode active material, for example.

(155) <<Particle Size>>

(156) A too large particle size of the positive electrode active material **904** causes problems such as difficulty in lithium diffusion and too much surface roughness of an active material layer in coating to a current collector. By contrast, a too small particle size causes problems such as difficulty in carrying the active material layer in coating to the current collector and overreaction with an electrolyte solution. Therefore, an average particle diameter (D50, also referred to as median diameter) is preferably more than or equal to 1 μm and less than or equal to 100 μm , further preferably more than or equal to 2 μm and less than or equal to 40 μm , still further preferably more than or equal to 5 μm and less than or equal to 30 μm .

(157) <Analysis Method>

(158) Whether or not a positive electrode active material has the pseudo-spinel crystal structure when charged with high voltage can be determined by analyzing a high-voltage charged positive electrode using XRD, electron diffraction, neutron diffraction, electron spin resonance (ESR), nuclear magnetic resonance (NMR), or the like. The XRD is particularly preferable because the symmetry of a transition metal such as cobalt contained in the positive electrode active material can be analyzed with high resolution, the degrees of crystallinity and the crystal orientations can be compared, the distortion of lattice periodicity and the crystallite size can be analyzed, and a positive electrode obtained by disassembling a secondary battery can be measured without any change with sufficient accuracy, for example.

(159) As described so far, the positive electrode active material **904** has a feature of a small change in the crystal structure between the high-voltage charged state and the discharged state. A material where 50 wt % or more of the crystal structure largely changes between the high-voltage charged state and the discharged state is not preferable because the material cannot withstand the high-voltage charge and discharge. In addition, it should be noted that an objective crystal structure is not obtained in some cases only by addition of impurity elements. For example, although the positive electrode active material that is lithium cobalt oxide containing magnesium and fluorine is a commonality, the positive electrode active material has 60 wt % or more of the pseudo-spinel crystal structure in some cases, and has 50 wt % or more of the H1-3 type crystal structure in other

cases, when charged with high voltage. Furthermore, at a predetermined voltage, the positive electrode active material has almost 100 wt % of the pseudo-spinel crystal structure, and with an increase in the predetermined voltage, the H1-3 type crystal structure is generated in some cases. Thus, the crystal structure of the positive electrode active material **904** is preferably analyzed by XRD or the like.

(160) Note that a positive electrode active material in the high-voltage charged state or the discharged state sometimes causes a change in the crystal structure when exposed to air. For example, the pseudo-spinel crystal structure changes into the H1-3 type crystal structure in some cases. Thus, all samples are preferably handled in an inert atmosphere such as an atmosphere including argon.

(161) <Positive Electrode Active Material **100C** of Comparative Example>

(162) The positive electrode active material **100C** shown in FIG. **10** is lithium cobalt oxide (LiCoO₂) to which halogen and magnesium are not added in a formation method described later. As described in Non-Patent Document 1, Non-Patent Document 2, and the like, the crystal structure of lithium cobalt oxide shown in FIG. **10** changes depending on the charge depth.

(163) As illustrated in FIG. **10**, lithium cobalt oxide with a charge depth of 0 (the discharged state) includes a region having the crystal structure of the space group R-3m, and includes three CoO₂ layers in a unit cell. Thus, this crystal structure is referred to as an O3-type crystal structure in some cases. Note that the CoO₂ layer has a structure in which octahedral geometry with oxygen atoms hexacoordinated to cobalt continues on a plane in the edge-sharing state.

(164) Furthermore, when the charge depth is 1, LiCoO₂ has the crystal structure of the space group P-3 ml, and one CoO₂ layer exists in a unit cell. Thus, this crystal structure is referred to as an O1-type crystal structure in some cases.

(165) Moreover, lithium cobalt oxide when the charge depth is approximately 0.88 has the crystal structure of the space group R-3m. This structure can also be regarded as a structure in which CoO₂ structures such as P-3 ml (O1) and LiCoO₂ structures such as R-3m (O3) are alternately stacked. Thus, this crystal structure is referred to as an H1-3 type crystal structure in some cases. Note that the number of cobalt atoms per unit cell in the actual H1-3 type crystal structure is twice as large as that of cobalt atoms per unit cell in other structures. However, in this specification including FIG. **10**, the c-axis of the H1-3 type crystal structure is described half that of the unit cell for easy comparison with the other structures.

(166) For the H1-3 type structure, as disclosed in Non-Patent Document 3, the coordinates of cobalt and oxygen in the unit cell can be expressed as follows, for example: Co (0, 0, 0.42150±0.00016), O₁ (0, 0, 0.27671±0.00045), and O₂ (0, 0, 0.11535±0.00045). O₁ and O₂ are each an oxygen atom. In this manner, the H1-3 type structure is represented by a unit cell including one cobalt and two oxygen. Meanwhile, the pseudo-spinel crystal structure of one embodiment of the present invention is preferably represented by a unit cell including one cobalt and one oxygen, as described later. This means that the symmetry of cobalt and oxygen differs between the pseudo-spinel structure and the H1-3 type structure, and the amount of change from the O₃ structure is smaller in the pseudo-spinel structure than in the H1-3 type structure. A preferred unit cell for representing a crystal structure in a positive electrode active material is selected such that the value of GOF (goodness of fit) is smaller in Rietveld analysis of XRD patterns, for example.

(167) When charge with a high voltage of 4.6 V or higher based on the redox potential of a lithium metal or charge with a large charge depth of 0.8 or more and discharge are repeated, the crystal structure of lithium cobalt oxide changes (i.e., an unbalanced phase change occurs) repeatedly between the H1-3 type structure and the R-3m (O3) structure in a discharged state.

(168) However, there is a large deviation in the position of the CoO₂ layer between these two crystal structures. As indicated by the dotted line and the arrow in FIG. **10**, the CoO₂ layer in the H1-3 type crystal structure largely deviates from that in R-3m (O3). Such a dynamic structural

change might adversely affect the stability of the crystal structure.

(169) A difference in volume is also large. A difference in volume in comparison with the same number of cobalt atoms between the H1-3 type crystal structure and the O3-type crystal structure in the discharged state is 3.0% or more.

(170) In addition, a structure in which CoO.sub.2 layers are continuous, such as P-3 ml (O1), included in the H1-3 type crystal structure is highly likely to be unstable.

(171) Thus, the repeated high-voltage charge and discharge break the crystal structure of lithium cobalt oxide. The break of the crystal structure degrades the cycle performance. This is probably because the break of the crystal structure reduces sites where lithium can stably exist and makes it difficult to insert and extract lithium.

Embodiment 4

(172) In this embodiment, examples of materials which can be used for a secondary battery including the positive electrode active material formed by the forming method of one embodiment of the present invention are described. In this embodiment, a secondary battery in which a positive electrode, a negative electrode, and an electrolyte solution are wrapped in an exterior body is described as an example.

(173) [Positive Electrode]

(174) The positive electrode includes a positive electrode active material layer and a positive electrode current collector.

(175) <Positive Electrode Active Material Layer>

(176) The positive electrode active material layer includes a positive electrode active material particle. The positive electrode active material layer may contain a conductive additive and a binder.

(177) As the positive electrode active material particle, the positive electrode active material formed by the forming method of one embodiment of the present invention can be used.

(178) Examples of the conductive additive include a carbon material, a metal material, and a conductive ceramic material. Alternatively, a fiber material may be used as the conductive additive. The content of the conductive additive with respect to the total amount of the active material layer is preferably greater than or equal to 1 wt % and less than or equal to 10 wt %, further preferably greater than or equal to 1 wt % and less than or equal to 5 wt %.

(179) A network for electric conduction can be formed in the electrode by the conductive additive. The conductive additive also allows maintaining of a path for electric conduction between the positive electrode active materials. The addition of the conductive additive to the active material layer increases the electric conductivity of the active material layer.

(180) Examples of the conductive additive include natural graphite, artificial graphite such as mesocarbon microbeads, and carbon fiber. Examples of carbon fiber include mesophase pitch-based carbon fiber and isotropic pitch-based carbon fiber. In addition, carbon nanofiber, carbon nanotube, or the like can be used as carbon fiber. Carbon nanotube can be formed by, for example, a vapor deposition method. Other examples of the conductive additive include carbon materials such as carbon black (e.g., acetylene black (AB)), graphite (black lead) particles, graphene, and fullerene. Alternatively, metal powder or metal fibers of copper, nickel, aluminum, silver, gold, or the like, a conductive ceramic material, or the like can be used.

(181) Alternatively, a graphene compound may be used as the conductive additive.

(182) A graphene compound has excellent electrical characteristics of high conductivity and excellent physical properties of high flexibility and high mechanical strength in some cases. Furthermore, a graphene compound has a planar shape. A graphene compound enables low-resistance surface contact. Furthermore, a graphene compound has extremely high conductivity even with a small thickness in some cases and thus allows a conductive path to be formed in an active material layer efficiently even with a small amount. For this reason, it is preferable to use a graphene compound as the conductive additive because the area where the active material and the

conductive additive are in contact with each other can be increased or electric resistance can be reduced in some cases. Here, it is particularly preferable to use, for example, graphene, multilayer graphene, or reduced graphene oxide (hereinafter, RGO) as a graphene compound. Note that RGO refers to a compound obtained by reducing graphene oxide (GO), for example.

(183) In the case where an active material particle with a small particle diameter, e.g., 1 μm or less, is used, the specific surface area of the active material particle is large and thus more conductive paths for connecting the active material particles are needed. In such a case, a graphene compound that can efficiently form a conductive path even in a small amount is particularly preferably used.

(184) A cross-sectional structure example of an active material layer **200** containing a graphene compound as a conductive additive is described below.

(185) FIG. **11A** shows a longitudinal cross-sectional view of the active material layer **200**. FIG. **11B** is an enlarged view of a region surrounded by dotted line in FIG. **11A**. The active material layer **200** includes a particulate positive electrode active material **101**, a graphene compound **201** serving as a conductive additive, and a binder (not illustrated). Here, graphene or multilayer graphene may be used as the graphene compound **201**, for example. The graphene compound **201** preferably has a sheet-like shape. The graphene compound **201** may have a sheet-like shape formed of a plurality of sheets of multilayer graphene and/or a plurality of sheets of graphene that partly overlap with each other.

(186) In the longitudinal cross section of the active material layer **200**, as illustrated in FIG. **11A**, the sheet-like graphene compounds **201** are dispersed substantially uniformly in the active material layer **200**. The graphene compounds **201** are schematically shown by thick lines in FIG. **11A** but are actually thin films each having a thickness corresponding to the thickness of a single layer or a multi-layer of carbon molecules. The plurality of graphene compounds **201** are formed in such a way as to wrap or cover the plurality of particulate positive electrode active materials **101** or adhere to the surfaces of the plurality of particulate positive electrode active materials **101**, so that the graphene compounds **201** make surface contact with the particulate positive electrode active materials **101**.

(187) Here, when the plurality of graphene compounds are bonded to each other, a net-like graphene compound sheet (hereinafter referred to as a graphene compound net or a graphene net) can be formed. The graphene net covering the active material can function as a binder for bonding active materials. The amount of a binder can thus be reduced, or the binder does not have to be used, increasing the proportion of the active material in the electrode volume or weight. That is to say, the capacity of the power storage device can be increased.

(188) Here, it is preferable that graphene oxide be used as the graphene compounds **201** and mixed with an active material to form a layer to be the active material layer **200**, and then reduction be performed. When graphene oxide with extremely high dispersibility in a polar solvent is used for the formation of the graphene compounds **201**, the graphene compounds **201** can be substantially uniformly dispersed in the active material layer **200**. The solvent is removed by volatilization from a dispersion medium in which graphene oxide is uniformly dispersed, and the graphene oxide is reduced; hence, the graphene compounds **201** remaining in the active material layer **200** partly overlap with each other and are dispersed such that surface contact is made, thereby forming a three-dimensional conductive path. Note that graphene oxide can be reduced either by heat treatment or with the use of a reducing agent, for example.

(189) Unlike a conductive additive in the form of particles, such as acetylene black, which makes point contact with an active material, the graphene compound **201** is capable of making low-resistance surface contact; accordingly, the electrical conduction between the particulate positive electrode active materials **101** and the graphene compound **201** can be improved with a smaller amount of the graphene compound **201** than that of a normal conductive additive. This increases the proportion of the positive electrode active material **101** in the active material layer **200**. Accordingly, the discharge capacity of the power storage device can be increased.

(190) As the binder, a rubber material such as styrene-butadiene rubber (SBR), styrene-isoprene-styrene rubber, acrylonitrile-butadiene rubber, butadiene rubber, or ethylene-propylene-diene copolymer can be used, for example. Alternatively, fluororubber can be used as the binder.

(191) As the binder, for example, water-soluble polymers are preferably used. As the water-soluble polymers, a polysaccharide and the like can be used. As the polysaccharide, a cellulose derivative such as carboxymethyl cellulose (CMC), methyl cellulose, ethyl cellulose, hydroxypropyl cellulose, diacetyl cellulose, or regenerated cellulose, starch, or the like can be used. It is more preferred that such water-soluble polymers be used in combination with any of the above rubber materials.

(192) Alternatively, as the binder, a material such as polystyrene, poly(methyl acrylate), poly(methyl methacrylate) (PMMA), sodium polyacrylate, polyvinyl alcohol (PVA), polyethylene oxide (PEO), polypropylene oxide, polyimide, polyvinyl chloride, polytetrafluoroethylene, polyethylene, polypropylene, polyisobutylene, polyethylene terephthalate, nylon, polyvinylidene fluoride (PVDF), polyacrylonitrile (PAN), ethylene-propylene-diene polymer, polyvinyl acetate, or nitrocellulose is preferably used.

(193) A plurality of the above materials may be used in combination for the binder.

(194) For example, a material having a significant viscosity modifying effect and another material may be used in combination. For example, a rubber material or the like has high adhesion or high elasticity but may have difficulty in viscosity modification when mixed in a solvent. In such a case, a rubber material or the like is preferably mixed with a material having a significant viscosity modifying effect, for example. As a material having a significant viscosity modifying effect, for example, a water-soluble polymer may be used. An example of a water-soluble polymer having an especially significant viscosity modifying effect is the above-mentioned polysaccharide; for example, a cellulose derivative such as carboxymethyl cellulose (CMC), methyl cellulose, ethyl cellulose, hydroxypropyl cellulose, diacetyl cellulose, or regenerated cellulose, or starch can be used.

(195) Note that a cellulose derivative such as carboxymethyl cellulose obtains a higher solubility when converted into a salt such as a sodium salt or an ammonium salt of carboxymethyl cellulose, and accordingly, easily exerts an effect as a viscosity modifier. The high solubility can also increase the dispersibility of an active material and other components in the formation of slurry for an electrode. In this specification, cellulose and a cellulose derivative used as a binder of an electrode include salts thereof.

(196) The water-soluble polymers stabilize viscosity by being dissolved in water and allow stable dispersion of the active material and another material combined as a binder such as styrene-butadiene rubber in an aqueous solution. Furthermore, a water-soluble polymer is expected to be easily and stably adsorbed to an active material surface because it has a functional group. Many cellulose derivatives such as carboxymethyl cellulose have functional groups such as a hydroxyl group and a carboxyl group, and because of the functional groups, polymers are expected to interact with each other and cover an active material surface in a large area.

(197) In the case where the binder covering or being in contact with the active material surface forms a film, the film is expected to serve as a passivation film to inhibit the decomposition of the electrolyte solution. Here, the passivation film refers to a film without electric conductivity or a film with extremely low electric conductivity, and can inhibit the decomposition of an electrolyte solution at a potential at which a battery reaction occurs in the case where the passivation film is formed on the active material surface, for example. It is preferred that the passivation film can conduct lithium ions while inhibiting electric conduction.

(198) <Positive Electrode Current Collector>

(199) For the positive electrode current collector, a material that has high conductivity, such as a metal like stainless steel, gold, platinum, aluminum, or titanium, or an alloy thereof, can be used. It is preferred that a material used for the positive electrode current collector not dissolve at the

potential of the positive electrode. It is also possible to use an aluminum alloy to which an element that improves heat resistance, such as silicon, titanium, neodymium, scandium, or molybdenum, is added. The positive electrode current collector can also be formed with a metal element that forms silicide by reacting with silicon. Examples of the metal element that forms silicide by reacting with silicon include zirconium, titanium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum, tungsten, cobalt, and nickel. The current collector can have any of various shapes including a foil-like shape, a plate-like shape (sheet-like shape), a net-like shape, a punching-metal shape, and an expanded-metal shape. The current collector preferably has a thickness of 5 μm to 30 μm .

(200) <Negative Electrode>

(201) The negative electrode includes a negative electrode active material layer and a negative electrode current collector. The negative electrode active material layer may contain a conductive additive and a binder.

(202) <Negative Electrode Active Material>

(203) As a negative electrode active material, for example, an alloy-based material or a carbon-based material can be used.

(204) For the negative electrode active material, an element which enables charge-discharge reactions by an alloying reaction and a dealloying reaction with lithium can be used. For example, a material containing at least one of silicon, tin, gallium, aluminum, germanium, lead, antimony, bismuth, silver, zinc, cadmium, indium, and the like can be used. Such elements have higher capacity than carbon; in particular, silicon has a high theoretical capacity of 4200 mAh/g. For this reason, silicon is preferably used as the negative electrode active material. Alternatively, a compound containing any of the above elements may be used. Examples of the compound include SiO , Mg.sub.2Si , Mg.sub.2Ge , SnO , SnO.sub.2 , Mg.sub.2Sn , SnS.sub.2 , V.sub.2Sn.sub.3 , FeSn.sub.2 , CoSn.sub.2 , Ni.sub.3Sn.sub.2 , Cu.sub.6Sn , Ag.sub.3Sn , Ag.sub.3Sb , Ni.sub.2MnSb , CeSb.sub.3 , LaSn.sub.3 , $\text{La.sub.3Co.sub.2Sn.sub.7}$, CoSb.sub.3 , InSb , and SbSn . Here, an element that enables charge-discharge reactions by an alloying reaction and a dealloying reaction with lithium, a compound containing the element, and the like may be referred to as an alloy-based material.

(205) In this specification and the like, SiO refers to silicon monoxide, for example. SiO can alternatively be expressed as SiO.sub.x . Here, x is preferably 1 or an approximate value of 1. For example, x is preferably 0.2 or more and 1.5 or less, further preferably 0.3 or more and 1.2 or less.

(206) As the carbon-based material, graphite, graphitizing carbon (soft carbon), non-graphitizing carbon (hard carbon), a carbon nanotube, graphene, carbon black, and the like can be used.

(207) Examples of graphite include artificial graphite and natural graphite. Examples of artificial graphite include meso-carbon microbeads (MCMB), coke-based artificial graphite, and pitch-based artificial graphite. As artificial graphite, spherical graphite having a spherical shape can be used. For example, MCMB is preferable because it may have a spherical shape. Moreover, MCMB is preferable in some cases because it can relatively easily have a small surface area. Examples of natural graphite include flake graphite and spherical natural graphite.

(208) Graphite has a low potential substantially equal to that of a lithium metal (higher than or equal to 0.05 V and lower than or equal to 0.3 V vs. Li/Li.sup.+) when lithium ions are intercalated into the graphite (while a lithium-graphite intercalation compound is formed). For this reason, a lithium ion secondary battery can have a high operating voltage. In addition, graphite is preferred because of its advantages such as a relatively high capacity per unit volume, relatively small volume expansion, low cost, and higher level of safety than that of a lithium metal.

(209) Alternatively, for the negative electrode active material, an oxide such as titanium dioxide (TiO.sub.2), lithium titanium oxide ($\text{Li.sub.4Ti.sub.15O.sub.12}$), lithium-graphite intercalation compound (Li.sub.xC.sub.6), niobium pentoxide (Nb.sub.2O.sub.5), tungsten oxide (WO.sub.2), or molybdenum oxide (MoO.sub.2) can be used.

(210) Still alternatively, for the negative electrode active material, $\text{Li}_{0.3-x}\text{M}_{0.3-x}\text{N}_x$ (M=Co, Ni, or Cu) with a $\text{Li}_{0.3}\text{N}$ structure, which is a nitride containing lithium and a transition metal, can be used. For example, $\text{Li}_{0.26}\text{Co}_{0.04}\text{N}_{0.3}$ is preferable because of high charge and discharge capacity (900 mAh/g and 1890 mAh/cm³).

(211) A nitride containing lithium and a transition metal is preferably used, in which case lithium ions are contained in the negative electrode active material and thus the negative electrode active material can be used in combination with a material for a positive electrode active material which does not contain lithium ions, such as V_2O_5 or Cr_3O_8 . In the case of using a material containing lithium ions as a positive electrode active material, the nitride containing lithium and a transition metal can be used for the negative electrode active material by extracting the lithium ions contained in the positive electrode active material in advance.

(212) Alternatively, a material which causes a conversion reaction can be used for the negative electrode active material. For example, a transition metal oxide which does not form an alloy with lithium, such as cobalt oxide (CoO), nickel oxide (NiO), and iron oxide (FeO), may be used for the negative electrode active material. Other examples of the material which causes a conversion reaction include oxides such as Fe_2O_3 , CuO, Cu_2O , RuO_2 , and Cr_2O_3 , sulfides such as $\text{CoS}_{0.89}$, NiS, and CuS, nitrides such as $\text{Zn}_{0.3}\text{N}_{0.2}$, $\text{Cu}_{0.3}\text{N}$, and $\text{Ge}_{0.3}\text{N}_{0.4}$, phosphides such as $\text{NiP}_{0.2}$, $\text{FeP}_{0.2}$, and $\text{CoP}_{0.3}$, and fluorides such as FeF_3 and BiF_3 .

(213) For the conductive additive and the binder that can be included in the negative electrode active material layer, materials similar to those of the conductive additive and the binder that can be included in the positive electrode active material layer can be used.

(214) <Negative Electrode Current Collector>

(215) For the negative electrode current collector, a material similar to that of the positive electrode current collector can be used. Note that a material that is not alloyed with a carrier ion such as lithium is preferably used for the negative electrode current collector.

(216) [Electrolyte Solution]

(217) The electrolyte solution contains a solvent and an electrolyte. As a solvent of the electrolyte solution, an aprotic organic solvent is preferably used; for example, one of ethylene carbonate (EC), propylene carbonate (PC), butylene carbonate, chloroethylene carbonate, vinylene carbonate, γ -butyrolactone, γ -valerolactone, dimethyl carbonate (DMC), diethyl carbonate (DEC), ethyl methyl carbonate (EMC), methyl formate, methyl acetate, ethyl acetate, methyl propionate, ethyl propionate, propyl propionate, methyl butyrate, 1,3-dioxane, 1,4-dioxane, dimethoxyethane (DME), dimethyl sulfoxide, diethyl ether, methyl diglyme, acetonitrile, benzonitrile, tetrahydrofuran, sulfolane, and sultone can be used, or two or more of these solvents can be used in an appropriate combination in an appropriate ratio.

(218) When one or more kinds of ionic liquids (room temperature molten salts) which have non-flammability and non-volatility is used as a solvent of the electrolyte solution, a power storage device can be prevented from exploding or catching fire even when the power storage device internally shorts out or the internal temperature increases owing to overcharging or the like. An ionic liquid is made with a cation and an anion, and contains an organic cation and an anion. Examples of the organic cation used for the electrolyte solution include aliphatic onium cations such as a quaternary ammonium cation, a tertiary sulfonium cation, and a quaternary phosphonium cation, and aromatic cations such as an imidazolium cation and a pyridinium cation. Examples of the anion used for the electrolyte solution include a monovalent amide-based anion, a monovalent methide-based anion, a fluorosulfonate anion, a perfluoroalkylsulfonate anion, a tetrafluoroborate anion, a perfluoroalkylborate anion, a hexafluorophosphate anion, and a perfluoroalkylphosphate anion.

(219) As an electrolyte dissolved in the above-described solvent, one of lithium salts such as LiPF_6 , LiClO_4 , LiAsF_6 , LiBF_4 , LiAlCl_4 , LiSCN , LiBr , LiI ,

Li.sub.2SO.sub.4, Li.sub.2B.sub.10Cl.sub.12, LiCF.sub.3SO.sub.3, LiC.sub.4F.sub.9SO.sub.3, LiC(CF.sub.3SO.sub.2).sub.3, LiC(C.sub.2FsSO.sub.2).sub.3, LiN(CF.sub.3SO.sub.2).sub.2, LiN(C.sub.4F.sub.9SO.sub.2)(CF.sub.3SO.sub.2), and LiN(C.sub.2FsSO.sub.2).sub.2 can be used, or two or more of these lithium salts can be used in an appropriate combination in an appropriate ratio.

(220) The electrolyte solution used for a storage device is preferably highly purified and contains a small amount of dust particles and elements other than the constituent elements of the electrolyte solution (hereinafter also simply referred to as impurities). Specifically, the weight ratio of impurities to the electrolyte solution is less than or equal to 1%, preferably less than or equal to 0.1%, and further preferably less than or equal to 0.01%.

(221) Furthermore, an additive agent such as vinylene carbonate, propane sultone (PS), tert-butylbenzene (TBB), fluoroethylene carbonate (FEC), lithium bis(oxalate)borate (LiBOB), or a dinitrile compound such as succinonitrile or adiponitrile may be added to the electrolyte solution. The concentration of the additive agent is, for example, higher than or equal to 0.1 wt % and lower than or equal to 5 wt % with respect to the whole solvent.

(222) Alternatively, a polymer gel electrolyte obtained in such a manner that a polymer is swelled with an electrolyte solution may be used.

(223) When a polymer gel electrolyte is used, safety against liquid leakage and the like is improved. Furthermore, a secondary battery can be thinner and more lightweight.

(224) As a polymer that undergoes gelation, a silicone gel, an acrylic gel, an acrylonitrile gel, a polyethylene oxide-based gel, a polypropylene oxide-based gel, a fluorine-based polymer gel, or the like can be used. Examples of the polymer include a polymer having a polyalkylene oxide structure, such as polyethylene oxide (PEO); PVDF; polyacrylonitrile; and a copolymer containing any of them. For example, PVDF-HFP, which is a copolymer of PVDF and hexafluoropropylene (HFP), can be used. The formed polymer may be porous.

(225) Instead of the electrolyte solution, a solid electrolyte including an inorganic material such as a sulfide-based inorganic material or an oxide-based inorganic material, or the like, or a solid electrolyte including a high-molecular material such as a polyethylene oxide (PEO)-based high-molecular material, or the like may be used. When the solid electrolyte is used, a separator and a spacer are not necessary. Furthermore, since the battery can be entirely solidified, there is no possibility of liquid leakage to increase the safety of the battery dramatically.

(226) Thus, the positive electrode active material formed by the forming method of one embodiment of the present invention can be applied to an all-solid-state battery. When the positive electrode active material is applied to an all-solid-state battery, the all-solid-state battery can have high safety and excellent characteristics.

Embodiment 5

(227) In this embodiment, examples of the shape of a secondary battery including the positive electrode active material formed by the forming method described in the above embodiment are described. For the materials used for the secondary battery described in this embodiment, the description of the above embodiments can be referred to.

(228) [Coin-Type Secondary Battery]

(229) First, an example of a coin-type secondary battery is described. FIG. 12A is an external view of a coin-type (single-layer flat type) secondary battery, and FIG. 12B is a cross-sectional view thereof.

(230) In a coin-type secondary battery **300**, a positive electrode can **301** doubling as a positive electrode terminal and a negative electrode can **302** doubling as a negative electrode terminal are insulated from each other and sealed by a gasket **303** made of polypropylene or the like. A positive electrode **304** includes a positive electrode current collector **305** and a positive electrode active material layer **306** provided in contact with the positive electrode current collector **305**. A negative electrode **307** includes a negative electrode current collector **308** and a negative electrode active

material layer **309** provided in contact with the negative electrode current collector **308**.

(231) Note that only one surface of each of the positive electrode **304** and the negative electrode **307** used for the coin-type secondary battery **300** is provided with an active material layer.

(232) For the positive electrode can **301** and the negative electrode can **302**, a metal having a corrosion-resistant property to an electrolyte solution, such as nickel, aluminum, or titanium, an alloy of such a metal, or an alloy of such a metal and another metal (e.g., stainless steel) can be used. Alternatively, the positive electrode can **301** and the negative electrode can **302** are preferably covered with nickel, aluminum, or the like in order to prevent corrosion due to the electrolyte solution. The positive electrode can **301** and the negative electrode can **302** are electrically connected to the positive electrode **304** and the negative electrode **307**, respectively.

(233) The negative electrode **307**, the positive electrode **304**, and the separator **310** are immersed in the electrolyte solution. Then, as illustrated in FIG. **12B**, the positive electrode **304**, the separator **310**, the negative electrode **307**, and the negative electrode can **302** are stacked in this order with the positive electrode can **301** positioned at the bottom, and the positive electrode can **301** and the negative electrode can **302** are subjected to pressure bonding with the gasket **303** located therebetween. In such a manner, the coin-type secondary battery **300** can be formed.

(234) When the positive electrode active material particle described in the above embodiments is used in the positive electrode **304**, the coin-type secondary battery **300** with little deterioration and high safety can be obtained.

(235) [Separator]

(236) The secondary battery preferably includes a separator. As the separator, for example, a fiber containing cellulose such as paper; nonwoven fabric; a glass fiber; ceramics; a synthetic fiber using nylon (polyamide), vinylon (polyvinyl alcohol-based fiber), polyester, acrylic, polyolefin, or polyurethane; or the like can be used. The separator is preferably formed to have an envelope-like shape to wrap one of the positive electrode and the negative electrode.

(237) The separator may have a multilayer structure. For example, an organic material film such as polypropylene or polyethylene can be coated with a ceramic-based material, a fluorine-based material, a polyamide-based material, a mixture thereof, or the like. Examples of the ceramic-based material include aluminum oxide particles and silicon oxide particles. Examples of the fluorine-based material include PVDF and polytetrafluoroethylene. Examples of the polyamide-based material include nylon and aramid (meta-based aramid and para-based aramid).

(238) Deterioration of the separator in charge and discharge at high voltage can be inhibited and thus the reliability of the secondary battery can be improved because oxidation resistance is improved when the separator is coated with the ceramic-based material. In addition, when the separator is coated with the fluorine-based material, the separator is easily brought into close contact with an electrode, resulting in high output characteristics. When the separator is coated with the polyamide-based material, in particular, aramid, the safety of the secondary battery is improved because heat resistance is improved.

(239) For example, both surfaces of a polypropylene film may be coated with a mixed material of aluminum oxide and aramid. Alternatively, a surface of the polypropylene film that is in contact with the positive electrode may be coated with the mixed material of aluminum oxide and aramid, and a surface of the polypropylene film that is in contact with the negative electrode may be coated with the fluorine-based material.

(240) With the use of a separator having a multilayer structure, the capacity per volume of the secondary battery can be increased because the safety of the secondary battery can be maintained even when the total thickness of the separator is small.

(241) [Cylindrical Secondary Battery]

(242) An example of a cylindrical secondary battery is described with reference to FIG. **13A** to FIG. **13D**. A cylindrical secondary battery **600** illustrated in FIG. **13A** includes, as illustrated in the cross-sectional schematic view of FIG. **13B**, a positive electrode cap (battery lid) **601** on the top

surface and a battery can (outer can) **602** on the side and bottom surfaces. The positive electrode cap and the battery can (outer can) **602** are insulated from each other by a gasket (insulating packing) **610**.

(243) Inside the battery can **602** having a hollow cylindrical shape, a battery element in which a strip-like positive electrode **604** and a strip-like negative electrode **606** are wound with a separator **605** located therebetween is provided. Although not illustrated, the battery element is wound around a center pin. One end of the battery can **602** is close and the other end thereof is open. For the battery can **602**, a metal having a corrosion-resistant property to an electrolyte solution, such as nickel, aluminum, or titanium, an alloy of such a metal, or an alloy of such a metal and another metal (e.g., stainless steel) can be used. Alternatively, the battery can **602** is preferably covered with nickel, aluminum, or the like in order to prevent corrosion due to the electrolyte solution. Inside the battery can **602**, the battery element in which the positive electrode, the negative electrode, and the separator are wound is provided between a pair of insulating plates **608** and **609** that face each other. Furthermore, a nonaqueous electrolyte solution (not illustrated) is injected inside the battery can **602** provided with the battery element. As the nonaqueous electrolyte solution, a nonaqueous electrolyte solution that is similar to that of the coin-type secondary battery can be used.

(244) Since the positive electrode and the negative electrode of the cylindrical secondary battery are wound, active materials are preferably formed on both sides of the current collectors. A positive electrode terminal (positive electrode current collecting lead) **603** is connected to the positive electrode **604**, and a negative electrode terminal (negative electrode current collecting lead) **607** is connected to the negative electrode **606**. Both the positive electrode terminal **603** and the negative electrode terminal **607** can be formed using a metal material such as aluminum. The positive electrode terminal **603** and the negative electrode terminal **607** are resistance-welded to a safety valve mechanism **612** and the bottom of the battery can **602**, respectively. The safety valve mechanism **612** is electrically connected to the positive electrode cap **601** through a PTC element (Positive Temperature Coefficient) **611**. The safety valve mechanism **612** cuts off electrical connection between the positive electrode cap **601** and the positive electrode **604** when the internal pressure of the battery exceeds a predetermined threshold value. The PTC element **611**, which serves as a thermally sensitive resistor whose resistance increases as temperature rises, limits the amount of current by increasing the resistance, thereby preventing abnormal heat generation. Barium titanate (BaTiO₃)-based semiconductor ceramic or the like can be used for the PTC element.

(245) Alternatively, as illustrated in FIG. 13C, a plurality of secondary batteries **600** may be sandwiched between a conductive plate **613** and a conductive plate **614** to form a module **615**. The plurality of secondary batteries **600** may be connected parallel to each other, connected in series, or connected in series after being connected parallel to each other. With the module **615** including the plurality of secondary batteries **600**, large electric power can be extracted.

(246) FIG. 13D is a top view of the module **615**. The conductive plate **613** is shown by a dotted line for clarity of the drawing. As illustrated in FIG. 13D, the module **615** may include a conducting wiring **616** which electrically connects the plurality of secondary batteries **600** to each other. It is possible to provide the conductive plate **613** over the conducting wiring **616** to overlap with each other. In addition, a temperature control device **617** may be provided between the plurality of secondary batteries **600**. When the secondary batteries **600** are overheated, the temperature control device **617** can cool them, and when the secondary batteries **600** are cooled too much, the temperature control device **617** can heat them. Thus, the performance of the module **615** is not easily influenced by the outside air temperature.

(247) When the positive electrode active material formed by the forming method described in the above embodiment is used in the positive electrode **604**, the cylindrical secondary battery **600** with little deterioration and high safety can be obtained.

(248) [Structural Examples of Power Storage Device]

(249) Other structural examples of power storage devices are described with reference to FIG. 14 to FIG. 18.

(250) FIG. 14A and FIG. 14B are external views of a power storage device. The power storage device includes a circuit board 900 and a secondary battery 913. A label 910 is attached onto the secondary battery 913. The power storage device further includes a terminal 951, a terminal 952, an antenna 914, and an antenna 915 as illustrated in FIG. 14B.

(251) The circuit board 900 includes a terminal 911 and a circuit 912. The terminal 911 is connected to the terminal 951, the terminal 952, the antenna 914, the antenna 915, and the circuit 912. Note that a plurality of terminals 911 serving as a control signal input terminal, a power supply terminal, and the like may be provided.

(252) The circuit 912 may be provided on the rear surface of the circuit board 900. Note that the shape of the antenna 914 and the antenna 915 is not limited to a coil shape and may be a linear shape or a plate shape. Furthermore, a planar antenna, an aperture antenna, a traveling-wave antenna, an EH antenna, a magnetic-field antenna, or a dielectric antenna may be used. The antenna 914 or the antenna 915 may be a flat-plate conductor. The flat-plate conductor can serve as one of conductors for electric field coupling. That is, the antenna 914 or the antenna 915 can serve as one of two conductors of a capacitor. Thus, electric power can be transmitted and received not only by an electromagnetic field or a magnetic field but also by an electric field.

(253) The line width of the antenna 914 is preferably larger than the line width of the antenna 915. This makes it possible to increase the amount of electric power received by the antenna 914.

(254) The power storage device includes a layer 916 between the secondary battery 913, and the antenna 914 and the antenna 915. The layer 916 has a function of, for example, blocking an electromagnetic field from the secondary battery 913. As the layer 916, for example, a magnetic body can be used.

(255) Note that the structure of the power storage device is not limited to that shown in FIG. 14.

(256) For example, as shown in FIG. 15A and FIG. 15B, two opposite surfaces of the secondary battery 913 illustrated in FIG. 14A and FIG. 14B may be provided with an antenna. FIG. 15A is an external view showing one side of the opposite surfaces, and FIG. 15B is an external view showing the other side of the opposite surfaces. For the same portions as those of the power storage device illustrated in FIG. 14A and FIG. 14B, a description of the power storage device illustrated in FIG. 14A and FIG. 14B can be referred to as appropriate.

(257) As illustrated in FIG. 15A, the antenna 914 is provided on one of the opposite surfaces of the secondary battery 913 with the layer 916 located therebetween, and as illustrated in FIG. 15B, the antenna 915 is provided on the other of the opposite surfaces of the secondary battery 913 with a layer 917 located therebetween. The layer 917 has a function of, for example, blocking an electromagnetic field from the secondary battery 913. As the layer 917, for example, a magnetic body can be used.

(258) With the above structure, both the antenna 914 and the antenna 915 can be increased in size.

(259) Alternatively, as illustrated in FIG. 15C and FIG. 15D, two opposite surfaces of the secondary battery 913 in FIG. 14A and FIG. 14B may be provided with different types of antennas. FIG. 15C is an external view showing one side of the opposite surfaces, and FIG. 15D is an external view showing the other side of the opposite surfaces. For the same portions as those of the power storage device illustrated in FIG. 14A and FIG. 14B, a description of the power storage device illustrated in FIG. 14A and FIG. 14B can be referred to as appropriate.

(260) As illustrated in FIG. 15C, the antenna 914 and the antenna 915 are provided on one of the opposite surfaces of the secondary battery 913 with the layer 916 interposed therebetween, and as illustrated in FIG. 15D, an antenna 918 is provided on the other of the opposite surfaces of the secondary battery 913 with the layer 917 interposed therebetween. The antenna 918 has a function of, for example, communicating data with an external device. An antenna with a shape that can be

applied to the antenna **914** and the antenna **915**, for example, can be used as the antenna **918**. As a system for communication using the antenna **918** between the power storage device and another device, a response method that can be used between the power storage device and another device, such as NFC, can be employed.

(261) Alternatively, as illustrated in FIG. **16A**, the secondary battery **913** in FIG. **14A** and FIG. **14B** may be provided with a display device **920**. The display device **920** is electrically connected to the terminal **911** via a terminal **919**. It is possible that the label **910** is not provided in a portion where the display device **920** is provided. For the same portions as those of the power storage device illustrated in FIG. **14A** and FIG. **14B**, a description of the power storage device illustrated in FIG. **14A** and FIG. **14B** can be referred to as appropriate.

(262) The display device **920** can display, for example, an image showing whether charging is being carried out, an image showing the amount of stored power, or the like. As the display device **920**, electronic paper, a liquid crystal display device, an electroluminescence (also referred to as EL) display device, or the like can be used. For example, the use of electronic paper can reduce the power consumption of the display device **920**.

(263) Alternatively, as illustrated in FIG. **16B**, the secondary battery **913** illustrated in FIG. **14A** and FIG. **14B** may be provided with a sensor **921**. The sensor **921** is electrically connected to the terminal **911** via a terminal **922**. For the same portions as those of the power storage device illustrated in FIG. **14A** and FIG. **14B**, a description of the power storage device illustrated in FIG. **14A** and FIG. **14B** can be referred to as appropriate.

(264) The sensor **921** has a function of measuring, for example, displacement, position, speed, acceleration, angular velocity, rotational frequency, distance, light, liquid, magnetism, temperature, chemical substance, sound, time, hardness, electric field, electric current, voltage, electric power, radiation, flow rate, humidity, gradient, oscillation, odor, or infrared rays. With the sensor **921**, for example, data on an environment (e.g., temperature) where the power storage device is placed can be sensed and stored in a memory inside the circuit **912**.

(265) Further structural examples of the secondary battery **913** are described with reference to FIG. **17** and FIG. **18**.

(266) The secondary battery **913** illustrated in FIG. **17A** includes a wound body **950** provided with the terminal **951** and the terminal **952** inside a housing **930**. The wound body **950** is soaked in an electrolyte solution inside the housing **930**. The terminal **952** is in contact with the housing **930**, and an insulator or the like inhibits contact between the terminal **951** and the housing **930**. Note that in FIG. **17A**, the housing **930** divided into two pieces is illustrated for convenience; however, in the actual structure, the wound body **950** is covered with the housing **930** and the terminal **951** and the terminal **952** extend to the outside of the housing **930**. For the housing **930**, a metal material (such as aluminum) or a resin material can be used.

(267) Note that as illustrated in FIG. **17B**, the housing **930** in FIG. **17A** may be formed using a plurality of materials. For example, in the secondary battery **913** in FIG. **17B**, a housing **930a** and a housing **930b** are bonded to each other, and the wound body **950** is provided in a region surrounded by the housing **930a** and the housing **930b**.

(268) For the housing **930a**, an insulating material such as an organic resin can be used. In particular, when a material such as an organic resin is used for the side on which an antenna is formed, blocking of an electric field from the secondary battery **913** can be inhibited. When an electric field is not significantly blocked by the housing **930a**, an antenna such as the antenna **914** and the antenna **915** may be provided inside the housing **930a**. For the housing **930b**, a metal material can be used, for example.

(269) FIG. **18** illustrates the structure of the wound body **950**. The wound body **950** includes a negative electrode **931**, a positive electrode **932**, and separators **933**. The wound body **950** is obtained by winding a sheet of a stack in which the negative electrode **931** overlaps with the positive electrode **932** with the separator **933** provided therebetween. Note that a plurality of stacks

each including the negative electrode **931**, the positive electrode **932**, and the separator **933** may be further stacked.

(270) The negative electrode **931** is connected to the terminal **911** illustrated in FIG. **14** via one of the terminal **951** and the terminal **952**. The positive electrode **932** is connected to the terminal **911** illustrated in FIG. **14** via the other of the terminal **951** and the terminal **952**.

(271) When the positive electrode active material particle described in the above embodiments is used in the positive electrode **932**, the secondary battery **913** with little deterioration and high safety can be obtained.

(272) [Laminated Secondary Battery]

(273) Next, an example of a laminated secondary battery is described with reference to FIG. **19** to FIG. **24**. When the laminated secondary battery has flexibility and is used in an electronic device at least part of which is flexible, the secondary battery can be bent as the electronic device is bent.

(274) A laminated secondary battery **980** is described with reference to FIG. **19A** to FIG. **19C**. The laminated secondary battery **980** includes a wound body **993** illustrated in FIG. **19A**. The wound body **993** includes a negative electrode **994**, a positive electrode **995**, and a separator **996**. The wound body **993** is, like the wound body **950** illustrated in FIG. **18**, obtained by winding a sheet of a stack in which the negative electrode **994** overlaps with the positive electrode **995** with the separator **996** therebetween.

(275) Note that the number of stacks each including the negative electrode **994**, the positive electrode **995**, and the separator **996** may be determined as appropriate depending on capacity and an element volume which are required. The negative electrode **994** is connected to a negative electrode current collector (not illustrated) via one of a lead electrode **997** and a lead electrode **998**, and the positive electrode **995** is connected to a positive electrode current collector (not illustrated) via the other of the lead electrode **997** and the lead electrode **998**.

(276) As illustrated in FIG. **19B**, the wound body **993** is packed in a space formed by bonding a film **981** and a film **982** having a depressed portion that serve as exterior bodies by thermocompression bonding or the like, whereby the secondary battery **980** can be formed as illustrated in FIG. **19C**. The wound body **993** includes the lead electrode **997** and the lead electrode **998**, and is soaked in an electrolyte solution inside a space surrounded by the film **981** and the film **982** having a depressed portion.

(277) For the film **981** and the film **982** having a depressed portion, a metal material such as aluminum or a resin material can be used, for example. With the use of a resin material for the film **981** and the film **982** having a depressed portion, the film **981** and the film **982** having a depressed portion can be changed in their forms when external force is applied; thus, a flexible storage battery can be formed.

(278) Although FIG. **19B** and FIG. **19C** illustrate an example where a space is formed by two films, the wound body **993** may be placed in a space formed by bending one film.

(279) When the positive electrode active material particle described in the above embodiments is used in the positive electrode **995**, the secondary battery **980** with little deterioration and high safety can be obtained.

(280) In FIG. **19A** to FIG. **19C**, an example in which the secondary battery **980** includes a wound body in a space formed by films serving as exterior bodies is described; however, as illustrated in FIG. **20**, a secondary battery may include a plurality of strip-shaped positive electrodes, a plurality of strip-shaped separators, and a plurality of strip-shaped negative electrodes in a space formed by films serving as exterior bodies, for example.

(281) A laminated secondary battery **500** illustrated in FIG. **20A** includes a positive electrode **503** including a positive electrode current collector **501** and a positive electrode active material layer **502**, a negative electrode **506** including a negative electrode current collector **504** and a negative electrode active material layer **505**, a separator **507**, an electrolyte solution **508**, and an exterior body **509**. The separator **507** is provided between the positive electrode **503** and the negative

electrode **506** in the exterior body **509**. The exterior body **509** is filled with the electrolyte solution **508**. The electrolyte solution described in Embodiment 4 can be used for the electrolyte solution **508**.

(282) In the laminated secondary battery **500** illustrated in FIG. **20A**, the positive electrode current collector **501** and the negative electrode current collector **504** also serve as terminals for an electrical contact with an external portion. For this reason, the positive electrode current collector **501** and the negative electrode current collector **504** may be arranged so as to be partly exposed to the outside of the exterior body **509**. Alternatively, without exposing the positive electrode current collector **501** and the negative electrode current collector **504** from the exterior body **509** to the outside, a lead electrode may be used, and the lead electrode and the positive electrode current collector **501** or the negative electrode current collector **504** may be bonded by ultrasonic welding so that the lead electrode is exposed to the outside.

(283) As the exterior body **509** of the laminated secondary battery **500**, for example, a laminate film having a three-layer structure can be employed in which a highly flexible metal thin film of aluminum, stainless steel, copper, nickel, or the like is provided over a film formed of a material such as polyethylene, polypropylene, polycarbonate, ionomer, or polyamide, and an insulating synthetic resin film of a polyamide-based resin, a polyester-based resin, or the like is provided over the metal thin film as the outer surface of the exterior body.

(284) FIG. **20B** illustrates an example of a cross-sectional structure of the laminated secondary battery **500**. Although FIG. **20A** illustrates an example including only two current collectors for simplicity, an actual battery includes a plurality of electrode layers.

(285) The example in FIG. **20B** includes 16 electrode layers. The secondary battery **500** has flexibility even though the secondary battery **500** includes 16 electrode layers. FIG. **20B** illustrates a structure including 8 layers of negative electrode current collectors **504** and 8 layers of positive electrode current collectors **501**, i.e., 16 layers in total. Note that FIG. **20B** illustrates a cross section of the extraction portion of the negative electrode, and the 8 negative electrode current collectors **504** are bonded to each other by ultrasonic welding. It is needless to say that the number of electrode layers is not limited to 16, and may be more than 16 or less than 16. With a large number of electrode layers, the secondary battery can have high capacity. With a small number of electrode layers, the secondary battery can have small thickness and high flexibility.

(286) FIG. **21** and FIG. **22** each illustrate an example of the external view of the laminated secondary battery **500**. In FIG. **21** and FIG. **22**, the positive electrode **503**, the negative electrode **506**, the separator **507**, the exterior body **509**, a positive electrode lead electrode **510**, and a negative electrode lead electrode **511** are included.

(287) FIG. **23A** illustrates external views of the positive electrode **503** and the negative electrode **506**. The positive electrode **503** includes the positive electrode current collector **501**, and the positive electrode active material layer **502** is formed on a surface of the positive electrode current collector **501**. The positive electrode **503** also includes a region where the positive electrode current collector **501** is partly exposed (hereinafter referred to as a tab region). The negative electrode **506** includes the negative electrode current collector **504**, and the negative electrode active material layer **505** is formed on a surface of the negative electrode current collector **504**. The negative electrode **506** also includes a region where the negative electrode current collector **504** is partly exposed, that is, a tab region. The areas and the shapes of the tab regions included in the positive electrode and the negative electrode are not limited to those illustrated in FIG. **23A**.

(288) [Method for Forming Laminated Secondary Battery]

(289) Here, an example of a method for forming the laminated secondary battery whose external view is illustrated in FIG. **21** is described with reference to FIG. **23B** and FIG. **23C**.

(290) First, the negative electrode **506**, the separator **507**, and the positive electrode **503** are stacked. FIG. **23B** illustrates a stack including the negative electrode **506**, the separator **507**, and the positive electrode **503**. An example described here includes 5 pairs of negative electrodes and 4

pairs of positive electrodes. Next, the tab regions of the positive electrodes **503** are bonded to each other, and the positive electrode lead electrode **510** is bonded to the tab region of the positive electrode on the outermost surface. The bonding can be performed by ultrasonic welding, for example. In a similar manner, the tab regions of the negative electrodes **506** are bonded to each other, and the negative electrode lead electrode **511** is bonded to the tab region of the negative electrode on the outermost surface.

(291) After that, the negative electrode **506**, the separator **507**, and the positive electrode **503** are placed over the exterior body **509**.

(292) Subsequently, the exterior body **509** is folded along a dashed line as illustrated in FIG. **23C**. Then, the outer edge of the exterior body **509** is bonded. The bonding can be performed by thermocompression bonding, for example. At this time, a part (or one side) of the exterior body **509** is left unbonded (to provide an inlet) so that the electrolyte solution **508** can be introduced later.

(293) Next, the electrolyte solution **508** is introduced into the exterior body **509** from the inlet of the exterior body **509**. The electrolyte solution **508** is preferably introduced in a reduced pressure atmosphere or in an inert atmosphere. Lastly, the inlet is bonded. In the above manner, the laminated secondary battery **500** can be formed.

(294) When the positive electrode active material particle described in the above embodiments is used in the positive electrode **503**, the secondary battery **500** with little deterioration and high safety can be obtained.

(295) [Bendable Secondary Battery]

(296) Next, an example of a bendable secondary battery is described with reference to FIG. **24** and FIG. **25**.

(297) FIG. **24A** is a schematic top view of a bendable battery **250**. FIG. **24B**, FIG. **24C**, and FIG. **24D** are schematic cross-sectional views taken along cutting line C1-C2, cutting line C3-C4, and cutting line A1-A2, respectively, in FIG. **24A**. The battery **250** includes an exterior body **251**, and a positive electrode **211a** and a negative electrode **211b** which are held in the exterior body **251**. A lead **212a** electrically connected to the positive electrode **211a** and a lead **212b** electrically connected to the negative electrode **211b** are extended to the outside of the exterior body **251**. In addition to the positive electrode **211a** and the negative electrode **211b**, an electrolyte solution (not illustrated) is enclosed in a region surrounded by the exterior body **251**.

(298) The positive electrode **211a** and the negative electrode **211b** included in the battery **250** are described with reference to FIG. **25**. FIG. **25A** is a perspective view illustrating the stacking order of the positive electrode **211a**, the negative electrode **211b**, and the separator **214**. FIG. **25B** is a perspective view illustrating the lead **212a** and the lead **212b** in addition to the positive electrode **211a** and the negative electrode **211b**.

(299) As illustrated in FIG. **25A**, the battery **250** includes a plurality of strip-shaped positive electrodes **211a**, a plurality of strip-shaped negative electrodes **211b**, and a plurality of separators **214**. The positive electrode **211a** and the negative electrode **211b** each include a projected tab portion and a portion other than the tab. A positive electrode active material layer is formed on one surface of the positive electrode **211a** other than the tab portion, and a negative electrode active material layer is formed on one surface of the negative electrode **211b** other than the tab portion.

(300) The positive electrodes **211a** and the negative electrodes **211b** are stacked so that surfaces of the positive electrodes **211a** on each of which the positive electrode active material layer is not formed are in contact with each other and that surfaces of the negative electrodes **211b** on each of which the negative electrode active material layer is not formed are in contact with each other.

(301) Furthermore, the separator **214** is provided between the surface of the positive electrode **211a** on which the positive electrode active material layer is formed and the surface of the negative electrode **211b** on which the negative electrode active material layer is formed. In FIG. **25**, the separator **214** is shown by a dotted line for easy viewing.

(302) In addition, as illustrated in FIG. **25B**, the plurality of positive electrodes **211a** are

electrically connected to the lead **212a** in a bonding portion **215a**. The plurality of negative electrodes **211b** are electrically connected to the lead **212b** in a bonding portion **215b**.

(303) Next, the exterior body **251** is described with reference to FIG. **24B**, FIG. **24C**, FIG. **24D**, and FIG. **24E**.

(304) The exterior body **251** has a film-like shape and is folded in half with the positive electrodes **211a** and the negative electrodes **211b** between facing portions of the exterior body **251**. The exterior body **251** includes a folded portion **261**, a pair of seal portions **262**, and a seal portion **263**. The pair of seal portions **262** is provided with the positive electrodes **211a** and the negative electrodes **211b** positioned therebetween and thus can also be referred to as side seals. The seal portion **263** has portions overlapping with the lead **212a** and the lead **212b** and can also be referred to as a top seal.

(305) Part of the exterior body **251** that overlaps with the positive electrodes **211a** and the negative electrodes **211b** preferably has a wave shape in which crest lines **271** and trough lines **272** are alternately arranged. The seal portions **262** and the seal portion **263** of the exterior body **251** are preferably flat.

(306) FIG. **24B** shows a cross section cut along the part overlapping with the crest line **271**. FIG. **24C** shows a cross section cut along the part overlapping with the trough line **272**. FIG. **24B** and FIG. **24C** correspond to cross sections of the battery **250**, the positive electrodes **211a**, and the negative electrodes **211b** in the width direction.

(307) Here, the distance between an end portion of the negative electrode **211b** in the width direction, that is, the end portion of the negative electrode **211b**, and the seal portion **262** is referred to as a distance L_a . When the battery **250** changes in shape such as bending, the positive electrode **211a** and the negative electrode **211b** change in shape such that the positions thereof are shifted from each other in the length direction as described later. At the time, if the distance L_a is too short, the exterior body **251** and the positive electrode **211a** and the negative electrode **211b** are rubbed hard against each other, so that the exterior body **251** is damaged in some cases. In particular, when a metal film of the exterior body **251** is exposed, there is concern that the metal film is corroded by the electrolyte solution. Thus, the distance L_a is preferably set as long as possible. However, a too long distance L_a increases the volume of the battery **250**.

(308) The distance L_a between the negative electrode **211b** and the seal portion **262** is preferably increased as the total thickness of the stacked positive electrodes **211a** and negative electrodes **211b** is increased.

(309) More specifically, when the total thickness of the stacked positive electrodes **211a** and negative electrodes **211b** is referred to as a thickness t , the distance L_a is preferably 0.8 times or more and 3.0 times or less, further preferably 0.9 times or more and 2.5 times or less, and still further preferably 1.0 times or more and 2.0 times or less as large as the thickness t . When the distance L_a is in this range, a compact battery which is highly reliable for bending can be obtained.

(310) Furthermore, when the distance between the pair of seal portions **262** is referred to as a distance L_b , it is preferable that the distance L_b be sufficiently longer than the width of the positive electrode **211a** and the negative electrode **211b** (here, a width W_b of the negative electrode **211b**). In this case, even when the positive electrode **211a** and the negative electrode **211b** come into contact with the exterior body **251** by change in the shape of the battery **250** such as repeated bending, the position of part of the positive electrode **211a** and the negative electrode **211b** can be shifted in the width direction; thus, the positive electrode **211a** and the negative electrode **211b** and the exterior body **251** can be effectively prevented from being rubbed against each other.

(311) For example, the difference between the distance L_b between the pair of seal portions **262** and the width W_b of the negative electrode **211b** is preferably 1.6 times or more and 6.0 times or less, further preferably 1.8 times or more and 5.0 times or less, and still further preferably 2.0 times or more and 4.0 times or less as large as the total thickness t of the positive electrode **211a** and the negative electrode **211b**.

(312) In other words, the distance L_b , the width W_b , and the thickness t preferably satisfy the relation of the following Formula 1.

(313)

[Formula 1]

$$\frac{L_b - W_b}{2t} \geq a \quad (\text{Formula 1})$$

(314) In the formula, a is 0.8 or more and 3.0 or less, preferably 0.9 or more and 2.5 or less, and further preferably 1.0 or more and 2.0 or less.

(315) FIG. 24D illustrates a cross section including the lead **212a** and corresponds to a cross section of the battery **250**, the positive electrode **211a**, and the negative electrode **211b** in the length direction. As illustrated in FIG. 24D, in the folded portion **261**, a space **273** is preferably provided between end portions of the positive electrode **211a** and the negative electrode **211b** in the length direction and the exterior body **251**.

(316) FIG. 24E is a schematic cross-sectional view of the battery **250** that is bent. FIG. 24E corresponds to a cross section along cutting line B1-B2 in FIG. 24A.

(317) When the battery **250** is bent, a part of the exterior body **251** positioned on the outer side in bending is stretched and the other part positioned on the inner side changes in shape as it shrinks. More specifically, the part of the exterior body **251** positioned on the outer side changes in shape such that the wave amplitude becomes smaller and the length of the wave period becomes larger. In contrast, the part of the exterior body **251** positioned on the inner side changes in shape such that the wave amplitude becomes larger and the length of the wave period becomes smaller. When the exterior body **251** changes in shape in this manner, stress applied to the exterior body **251** due to bending is relieved, so that a material itself that forms the exterior body **251** does not need to expand and contract. As a result, the battery **250** can be bent with weak force without damage to the exterior body **251**.

(318) Furthermore, as illustrated in FIG. 24E, when the battery **250** is bent, the positions of the positive electrode **211a** and the negative electrode **211b** are shifted relatively. At this time, ends of the stacked positive electrodes **211a** and negative electrodes **211b** on the seal portion **263** side are fixed by a fixing member **217**; thus, the plurality of positive electrodes **211a** and the plurality of negative electrodes **211b** are more shifted at a position closer to the folded portion **261**. Therefore, stress applied to the positive electrode **211a** and the negative electrode **211b** is relieved, and the positive electrode **211a** and the negative electrode **211b** themselves do not need to expand and contract. As a result, the battery **250** can be bent without damage to the positive electrode **211a** and the negative electrode **211b**.

(319) Furthermore, the space **273** provided between the positive electrode **211a** and the negative electrode **211b** and the exterior body **251** enables the positive electrode **211a** and the negative electrode **211b** located on an inner side to be shifted relatively without being in contact with the exterior body **251** when the battery **250** is bent.

(320) In the battery **250** illustrated in FIG. 24 and FIG. 25, the exterior body, the positive electrode

211a, and the negative electrode **211b** are less likely to be damaged and the battery characteristics are less likely to deteriorate even when the battery **250** is repeatedly bent and unbent. When the positive electrode active material particle described in the above embodiments is used for the positive electrode **211a** included in the battery **250**, a secondary battery with little deterioration and high safety can be obtained.

Embodiment 6

(321) In this embodiment, examples of electronic devices including the secondary battery of one embodiment of the present invention are described.

(322) First, FIG. **26** shows examples of electronic devices including the bendable secondary battery described in Embodiment 4. Examples of an electronic device including a bendable secondary battery include television sets (also referred to as televisions or television receivers), monitors of computers or the like, digital cameras, digital video cameras, digital photo frames, mobile phones (also referred to as cellular phones or mobile phone devices), portable game machines, portable information terminals, audio reproducing devices, and large game machines such as pachinko machines.

(323) In addition, a flexible secondary battery can be incorporated along a curved inside/outside wall surface of a house or a building or a curved interior/exterior surface of an automobile.

(324) FIG. **26A** illustrates an example of a mobile phone. A mobile phone **7400** is provided with a display portion **7402** incorporated in a housing **7401**, an operation button **7403**, an external connection port **7404**, a speaker **7405**, a microphone **7406**, and the like. Note that the mobile phone **7400** includes a secondary battery **7407**.

(325) FIG. **26B** illustrates the mobile phone **7400** that is bent. When the whole mobile phone **7400** is curved by external force, the secondary battery **7407** included in the mobile phone **7400** is also curved. FIG. **26C** illustrates the curved secondary battery **7407**. The secondary battery **7407** is a thin secondary battery. The secondary battery **7407** is curved and fixed. Note that the secondary battery **7407** includes a lead electrode electrically connected to a current collector.

(326) FIG. **26D** illustrates an example of a bangle display device. A portable display device **7100** includes a housing **7101**, a display portion **7102**, an operation button **7103**, and a secondary battery **7104**. FIG. **26E** illustrates the bent secondary battery **7104**. When the curved secondary battery **7104** is on a user's arm, the housing changes its form and the curvature of a part or the whole of the secondary battery **7104** is changed. Note that the radius of curvature of a curve at a point refers to the radius of the circular arc that best approximates the curve at that point, and the reciprocal of the radius of curvature is referred to as a curvature. Specifically, part or the whole of the housing or the main surface of the secondary battery **7104** is changed in the range of radius of curvature from 40 mm to 150 mm. When the radius of curvature at the main surface of the secondary battery **7104** is greater than or equal to 40 mm and less than or equal to 150 mm, the reliability can be kept high.

(327) FIG. **26F** illustrates an example of a watch-type portable information terminal. A portable information terminal **7200** includes a housing **7201**, a display portion **7202**, a band **7203**, a buckle **7204**, an operation button **7205**, an input output terminal **7206**, and the like.

(328) The portable information terminal **7200** is capable of executing a variety of applications such as mobile phone calls, e-mailing, viewing and editing texts, music reproduction, Internet communication, and a computer game.

(329) The display surface of the display portion **7202** is curved, and images can be displayed on the curved display surface. In addition, the display portion **7202** includes a touch sensor, and operation can be performed by touching the screen with a finger, a stylus, or the like. For example, by touching an icon **7207** displayed on the display portion **7202**, application can be started.

(330) With the operation button **7205**, a variety of functions such as time setting, power on/off, on/off of wireless communication, setting and cancellation of a silent mode, and setting and cancellation of a power saving mode can be performed. For example, the functions of the operation button **7205** can be set freely by setting the operating system incorporated in the portable

information terminal **7200**.

(331) The portable information terminal **7200** can employ near field communication that is standardized communication. For example, mutual communication between the portable information terminal **7200** and a headset capable of wireless communication can be performed, and thus hands-free calling is possible.

(332) Moreover, the portable information terminal **7200** includes the input output terminal **7206**, and data can be directly transmitted to and received from another information terminal via a connector. In addition, charging via the input output terminal **7206** is possible. Note that the charging operation may be performed by wireless power feeding without using the input output terminal **7206**.

(333) The display portion **7202** of the portable information terminal **7200** includes the secondary battery of one embodiment of the present invention. For example, the secondary battery **7104** illustrated in FIG. **26E** can be provided in the housing **7201** while being curved, or can be provided in the band **7203** such that it can be curved.

(334) The portable information terminal **7200** preferably includes a sensor. As the sensor, for example, a human body sensor such as a fingerprint sensor, a pulse sensor, or a temperature sensor, a touch sensor, a pressure sensitive sensor, an acceleration sensor, or the like is preferably mounted.

(335) FIG. **26G** illustrates an example of an armband display device. A display device **7300** includes a display portion **7304** and the secondary battery of one embodiment of the present invention. The display device **7300** can include a touch sensor in the display portion **7304** and can serve as a portable information terminal.

(336) The display surface of the display portion **7304** is bent, and images can be displayed on the bent display surface. In addition, the display state of the display device **7300** can be changed by, for example, near field communication that is standardized communication, or the like.

(337) The display device **7300** includes an input output terminal, and data can be directly transmitted to and received from another information terminal via a connector. In addition, charging via the input output terminal is possible. Note that the charging operation may be performed by wireless power feeding without using the input output terminal.

(338) Next, FIG. **27A** and FIG. **27B** illustrate an example of a foldable tablet terminal. A tablet terminal **9600** illustrated in FIG. **27A** and FIG. **27B** includes a housing **9630a**, a housing **9630b**, a movable portion **9640** connecting the housing **9630a** and the housing **9630b**, a display portion **9631**, a display mode changing switch **9626**, a power switch **9627**, a power saving mode changing switch **9625**, a fastener **9629**, and an operation switch **9628**. A flexible panel is used for the display portion **9631**, whereby a tablet terminal with a larger display portion can be provided. FIG. **27A** illustrates the tablet terminal **9600** that is opened, and FIG. **27B** illustrates the tablet terminal **9600** that is closed.

(339) The tablet terminal **9600** includes a power storage unit **9635** inside the housing **9630a** and the housing **9630b**. The power storage unit **9635** is provided across the housing **9630a** and the housing **9630b**, passing through the movable portion **9640**.

(340) Part of the display portion **9631** can be a touch panel region and data can be input when a displayed operation key is touched. When a position where a keyboard display switching button is displayed on the touch panel is touched with a finger, a stylus, or the like, keyboard buttons can be displayed on the display portion **9631**.

(341) The display mode switch **9626** can switch the display between a portrait mode and a landscape mode, and between monochrome display and color display, for example. The power saving mode changing switch **9625** can control display luminance in accordance with the amount of external light in use of the tablet terminal **9600**, which is measured with an optical sensor incorporated in the tablet terminal **9600**. Another detection device including a sensor for detecting inclination, such as a gyroscope sensor or an acceleration sensor, may be incorporated in the tablet terminal, in addition to the optical sensor.

(342) The tablet terminal is closed in FIG. 27B. The tablet terminal includes the housing **9630**, a solar cell **9633**, and a charge and discharge control circuit **9634** including a DC-DC converter **9636**. The secondary battery of one embodiment of the present invention is used as the power storage unit **9635**.

(343) The tablet terminal **9600** can be folded such that the housing **9630a** and the housing **9630b** overlap with each other when not in use. By the folding, the display portion **9631** can be protected, which increases the durability of the tablet terminal **9600**. Since the power storage unit **9635** using the secondary battery of one embodiment of the present invention has high capacity and excellent cycle performance, the tablet terminal which can be used for a long time for a long period can be provided.

(344) The tablet terminal illustrated in FIG. 27A and FIG. 27B can also have a function of displaying various kinds of data (e.g., a still image, a moving image, and a text image), a function of displaying a calendar, a date, or the time on the display portion, a touch-input function of operating or editing data displayed on the display portion by touch input, a function of controlling processing by various kinds of software (programs), and the like.

(345) The solar cell **9633**, which is attached on the surface of the tablet terminal, supplies electric power to a touch panel, a display portion, an image signal processor, and the like. Note that the solar cell **9633** can be provided on one or both surfaces of the housing **9630** and the power storage unit **9635** can be charged efficiently.

(346) The structure and operation of the charge and discharge control circuit **9634** illustrated in FIG. 27B are described with reference to a block diagram in FIG. 27C. The solar cell **9633**, the power storage unit **9635**, the DC-DC converter **9636**, a converter **9637**, switches SW1 to SW3, and the display portion **9631** are illustrated in FIG. 27C, and the power storage unit **9635**, the DC-DC converter **9636**, the converter **9637**, and the switches SW1 to SW3 correspond to the charge and discharge control circuit **9634** in FIG. 27B.

(347) First, an example of the operation in the case where power is generated by the solar cell **9633** using external light is described. The voltage of electric power generated by the solar cell is raised or lowered by the DC-DC converter **9636** to a voltage for charging the power storage unit **9635**. When the power from the solar cell **9633** is used for the operation of the display portion **9631**, the switch SW1 is turned on and the voltage of the power is raised or lowered by the converter **9637** to a voltage needed for operating the display portion **9631**. When display on the display portion **9631** is not performed, the switch SW1 is turned off and the switch SW2 is turned on, so that the power storage unit **9635** can be charged.

(348) Note that the solar cell **9633** is described as an example of a power generation means; however, one embodiment of the present invention is not limited to this example. The power storage unit **9635** may be charged using another power generation means such as a piezoelectric element or a thermoelectric conversion element (Peltier element). For example, the power storage unit **9635** may be charged with a non-contact power transmission module that transmits and receives power wirelessly (without contact) to charge the battery or with a combination of other charging means.

(349) FIG. 28 illustrates other examples of electronic devices. In FIG. 28, a display device **8000** is an example of an electronic device using a secondary battery **8004** of one embodiment of the present invention. Specifically, the display device **8000** corresponds to a display device for TV broadcast reception and includes a housing **8001**, a display portion **8002**, speaker portions **8003**, the secondary battery **8004**, and the like. The secondary battery **8004** of one embodiment of the present invention is provided in the housing **8001**. The display device **8000** can receive electric power from a commercial power supply, or use electric power stored in the secondary battery **8004**. Thus, the display device **8000** can operate with the use of the secondary battery **8004** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(350) A semiconductor display device such as a liquid crystal display device, a light-emitting device in which a light-emitting element such as an organic EL element is provided in each pixel, an electrophoretic display device, a DMD (Digital Micromirror Device), a PDP (Plasma Display Panel), or an FED (Field Emission Display) can be used for the display portion **8002**.

(351) Note that the display device includes, in its category, all of information display devices for personal computers, advertisement displays, and the like other than TV broadcast reception.

(352) In FIG. **28**, an installation lighting device **8100** is an example of an electronic device using a secondary battery **8103** of one embodiment of the present invention. Specifically, the lighting device **8100** includes a housing **8101**, a light source **8102**, the secondary battery **8103**, and the like. Although FIG. **28** illustrates the case where the secondary battery **8103** is provided in a ceiling **8104** on which the housing **8101** and the light source **8102** are installed, the secondary battery **8103** may be provided in the housing **8101**. The lighting device **8100** can receive electric power from a commercial power supply, or use electric power stored in the secondary battery **8103**. Thus, the lighting device **8100** can operate with the use of the secondary battery **8103** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(353) Note that although the installation lighting device **8100** provided in the ceiling **8104** is illustrated in FIG. **28** as an example, the secondary battery of one embodiment of the present invention can be used for an installation lighting device provided in, for example, a sidewall **8105**, a floor **8106**, a window **8107**, or the like other than the ceiling **8104**, or can be used in a tabletop lighting device or the like.

(354) As the light source **8102**, an artificial light source which emits light artificially by using power can be used. Specifically, an incandescent lamp, a discharge lamp such as a fluorescent lamp, and a light-emitting element such as an LED or an organic EL element are given as examples of the artificial light source.

(355) In FIG. **28**, an air conditioner including an indoor unit **8200** and an outdoor unit **8204** is an example of an electronic device including a secondary battery **8203** of one embodiment of the present invention. Specifically, the indoor unit **8200** includes a housing **8201**, an air outlet **8202**, the secondary battery **8203**, and the like. Although FIG. **28** illustrates the case where the secondary battery **8203** is provided in the indoor unit **8200**, the secondary battery **8203** may be provided in the outdoor unit **8204**. Alternatively, the secondary batteries **8203** may be provided in both the indoor unit **8200** and the outdoor unit **8204**. The air conditioner can receive electric power from a commercial power supply, or use electric power stored in the secondary battery **8203**. Particularly in the case where the secondary batteries **8203** are provided in both the indoor unit **8200** and the outdoor unit **8204**, the air conditioner can operate with the use of the secondary battery **8203** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(356) Note that although the split-type air conditioner including the indoor unit and the outdoor unit is illustrated in FIG. **28** as an example, the secondary battery of one embodiment of the present invention can be used in an air conditioner in which the functions of an indoor unit and an outdoor unit are integrated in one housing.

(357) In FIG. **28**, an electric refrigerator-freezer **8300** is an example of an electronic device using a secondary battery **8304** of one embodiment of the present invention. Specifically, the electric refrigerator-freezer **8300** includes a housing **8301**, a refrigerator door **8302**, a freezer door **8303**, the secondary battery **8304**, and the like. The secondary battery **8304** is provided in the housing **8301** in FIG. **28**. The electric refrigerator-freezer **8300** can receive electric power from a commercial power supply, or use electric power stored in the secondary battery **8304**. Thus, the electric refrigerator-freezer **8300** can operate with the use of the secondary battery **8304** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(358) In addition, power can be stored in the secondary battery in a time period when electronic devices are not used, particularly when the proportion of the amount of power which is actually used to the total amount of power which can be supplied from a commercial power source (such a proportion referred to as a usage rate of power) is low, whereby an increase in the usage rate of power can be reduced in a time period when the electronic devices are used. For example, in the case of the electric refrigerator-freezer **8300**, power is stored in the secondary battery **8304** in night time when the temperature is low and the refrigerator door **8302** and the freezer door **8303** are not opened and closed. On the other hand, in daytime when the temperature is high and the refrigerator door **8302** and the freezer door **8303** are opened and closed, the secondary battery **8304** is used as an auxiliary power source; thus, the usage rate of power in daytime can be reduced.

(359) The secondary battery of one embodiment of the present invention can be used in a variety of electronic devices as well as the above electronic devices. According to one embodiment of the present invention, the secondary battery can have little deterioration and high safety. Thus, when the secondary battery of one embodiment of the present invention is used in the electronic devices described in this embodiment, electronic devices with longer lifetime and higher safety can be obtained. This embodiment can be implemented in appropriate combination with the other embodiments.

Embodiment 7

(360) In this embodiment, examples of vehicles including the secondary battery of one embodiment of the present invention are described.

(361) The use of secondary batteries in vehicles enables production of next-generation clean energy vehicles such as hybrid electric vehicles (HVs), electric vehicles (EVs), and plug-in hybrid electric vehicles (PHVs or PHEVs).

(362) FIG. **29** illustrates examples of a vehicle using the secondary battery of one embodiment of the present invention. An automobile **8400** illustrated in FIG. **29A** is an electric vehicle that runs on the power of an electric motor. Alternatively, the automobile **8400** is a hybrid electric vehicle capable of driving appropriately using either an electric motor or an engine. The use of a secondary battery of one embodiment of the present invention can provide a high-mileage vehicle. The automobile **8400** includes the secondary battery. The secondary battery is used not only for driving an electric motor **8406**, but also for supplying electric power to a light-emitting device such as a headlight **8401** or a room light (not illustrated).

(363) The secondary battery can also supply electric power to a display device of a speedometer, a tachometer, or the like included in the automobile **8400**. Furthermore, the secondary battery can supply electric power to a semiconductor device included in the automobile **8400**, such as a navigation system.

(364) An automobile **8500** illustrated in FIG. **29B** can be charged when a secondary battery **8024** included in the automobile **8500** is supplied with electric power through external charging equipment by a plug-in system, a contactless power feeding system, or the like. In FIG. **29B**, the secondary battery **8024** mounted on the automobile **8500** is charged with the use of a ground-based charging apparatus **8021** through a cable **8022**. In charging, a given method such as CHAdeMO (registered trademark) or Combined Charging System may be employed as a charging method, a connector, or the like as appropriate. The charging apparatus **8021** may be a charging station provided in a commerce facility or a power source in a house. With the use of a plug-in technique, the secondary battery **8024** mounted on the automobile **8500** can be charged by being supplied with electric power from the outside, for example. The charging can be performed by converting AC electric power into DC electric power through a converter such as an AC-DC converter.

(365) Furthermore, although not illustrated, the vehicle may include a power receiving device so that it can be charged by being supplied with electric power from an above-ground power transmitting device in a contactless manner. In the case of the contactless power feeding system, by fitting a power transmitting device in a road or an exterior wall, charging can be performed not

only when the vehicle stops but also when moves. In addition, the contactless power feeding system may be utilized to perform transmission and reception of electric power between vehicles. A solar cell may be provided in the exterior of the vehicle to charge the secondary battery when the vehicle stops or moves. To supply electric power in such a contactless manner, an electromagnetic induction method or a magnetic resonance method can be used.

(366) FIG. 29C shows an example of a motorcycle using the secondary battery of one embodiment of the present invention. A motor scooter **8600** illustrated in FIG. 29C includes a secondary battery **8602**, side mirrors **8601**, and indicators **8603**. The secondary battery **8602** can supply electric power to the indicators **8603**.

(367) Furthermore, in the motor scooter **8600** illustrated in FIG. 29C, the secondary battery **8602** can be held in a storage unit under seat **8604**. The secondary battery **8602** can be held in the storage unit under seat **8604** even with a small size.

(368) According to one embodiment of the present invention, the secondary battery can have little deterioration and high safety. Thus, when the secondary battery is mounted on a vehicle, a reduction in mileage, acceleration performance, or the like can be inhibited. In addition, a highly safe vehicle can be achieved. Furthermore, the secondary battery mounted on the vehicle can be used as a power source for supplying electric power to products other than the vehicle. In such a case, the use of a commercial power source can be avoided at peak time of electric power demand, for example. If the use of a commercial power source can be avoided at peak time of electric power demand, the avoidance can contribute to energy saving and a reduction in carbon dioxide emissions. Moreover, the secondary battery with little deterioration and high safety can be used for a long period; thus, the use amount of rare metals such as cobalt can be reduced.

(369) This embodiment can be implemented in appropriate combination with the other embodiments.

Example 1

(370) In this example, LiMO.sub.2 formed by the forming method of one embodiment of the present invention is described. The forming method is described with reference to FIG. 1, FIG. 4A, and Table 2.

(371) <Formation of Samples of LiMO.sub.2>

(372) First, the mixture **902** containing magnesium and fluorine was formed (Steps Step S11 to Step S14). LiF and MgF.sub.2 were weighted so that the molar ratio of LiF to MgF.sub.2 was LiF:MgF.sub.2=1:3, acetone was added as a solvent, and the materials were mixed and ground by a wet process. The mixing and the grinding were performed in a ball mill using a zirconia ball at 400 rpm for 12 hour. The material that has been subjected to the treatment was collected to be the mixture **902**.

(373) Next, lithium cobalt oxide was prepared as a composite oxide containing lithium and cobalt. More specifically, CELLSEED C-10N formed by NIPPON CHEMICAL INDUSTRIAL CO., LTD. was prepared as a composite oxide (Step S25).

(374) Next, in Step S31, the materials were weighed so that the atomic weight of magnesium in the mixture **902** was 0.5 mol % of the atomic weight of cobalt in the lithium cobalt oxide. The mixing was performed by a dry method. The mixing was performed in a ball mill using a zirconia ball at 150 rpm for 1 hour.

(375) Next, the mixture **903** was put into an alumina crucible (aluminum oxide crucible) and annealed in a muffle furnace (Step S34). The annealing conditions are different between the samples and are shown in Table 2. The temperature rising rate was 200° C./h, and the temperature decreasing time was longer than or equal to 10 hours. The material after the heat treatment was collected and made to pass through a sieve (Step S35), so that each sample (Comparative sample 1 and Sample 2) was obtained (Step S36). FIG. 30 shows the alumina crucible that was actually used. FIG. 30A shows the alumina crucible not covered with a lid yet, and FIG. 30B shows the alumina crucible covered with the lid.

(376) Sample 2 was formed by the forming method of one embodiment of the present invention. Comparative sample 1 and Sample 2 are different in the condition of an atmosphere including LiF.

(377) TABLE-US-00002 TABLE 2 Sample Annealing Annealing O.sub.2 Atmosphere weight temperature time condi- including (g) (° C.) (h) tion LiF Comparative 30 900 20 flow No sample 1 Sample 2 30 900 20 flow Yes

<Annealing Methods of Samples of LiMO.sub.2>

(378) The steps up to S33 were the same in all the samples. The annealing method in S34 was different between the samples. A conceptual view at the time of the annealing is illustrated in FIG. 4A.

(379) In Table 2, “Sample weight” is weight of the annealed mixture 903.

(380) In Table 2, “Annealing temperature” is a temperature at the time of the annealing, and “Annealing time” is time for holding the annealing temperature.

(381) In Table 2, “O.sub.2 condition” means a method for introducing O.sub.2 into the space 102 in the heating furnace, and “flow” shows that the annealing was performed while O.sub.2 is introduced at a flow rate of 10 L/min.

(382) In Table 2, “Atmosphere including LiF” shows whether or not the container 122 and the fluoride 906 (LiF in this example) were heated at the same time as the annealing of the mixture 903, “No” shows the case where only the mixture 903 was annealed without the use of the container 122 and the fluoride 906, and “Yes” shows the case where the container 122 and the fluoride 906 were heated at the same time as the mixture 903. Note that in the case of “Yes”, four containers 122 each including 1 g of LiF were provided in the space 102 in the heating furnace.

(383) <Formation of Battery Cell>

(384) Next, positive electrodes were formed using Comparative sample 1 and Sample 2 formed in the above as positive electrode active materials. A current collector that was coated with slurry in which the positive electrode active material, AB, and PVDF were mixed at the active material:AB:PVDF=95:3:2 (weight ratio) was used. As a solvent of the slurry, NMP was used.

(385) After the current collector was coated with the slurry, the solvent was volatilized. Then, pressure was applied at 210 kN/m, and then pressure was applied at 1467 kN/m. Through the above process, the positive electrode was obtained. The carried amount of the positive electrode was approximately 7 mg/cm.sup.2, and the electrode density was >3.8 g/cc.

(386) Using the formed positive electrodes, CR2032 type coin battery cells (a diameter of 20 mm, a height of 3.2 mm) were formed.

(387) A lithium metal was used for a counter electrode.

(388) As an electrolyte contained in the electrolyte solution, 1 mol/L lithium hexafluorophosphate (LiPF.sub.6) was used. As the electrolyte solution, an electrolyte solution in which ethylene carbonate (EC) and diethyl carbonate (DEC) were mixed at EC:DEC=3:7 (volume ratio) was used. Note that for secondary batteries used for evaluating the charge and discharge efficiency, 2 wt % of vinylene carbonate (VC) was added to the electrolytic solution.

(389) As a separator, 25-μm-thick polypropylene was used.

(390) A positive electrode can and a negative electrode can that were formed using stainless steel (SUS) were used.

(391) <Measurement of Charge and Discharge Efficiency>

(392) The cycle performance of the battery cells formed using the comparative sample and Sample 2 that were obtained was measured. The cycle performance was evaluated at 25° C. while the CCCV charging (1.0 C, 4.6 V, a termination current of 0.1 C) and the CC discharging (1.0 C, 2.5 V) were performed. FIG. 31 shows the results.

(393) It is found from FIG. 31 that Sample 2 that was formed by one embodiment of the present invention shows cycle performance superior to that of Comparative sample 1. Thus, annealing in an atmosphere including LiF enables a positive electrode active material having excellent characteristics to be formed.

REFERENCE NUMERALS

(394) **100**: heating furnace, **101**: positive electrode active material, **100A-1**: positive electrode active material, **100C**: positive electrode active material, **102**: space in heating furnace, **104**: hot plate, **106**: heater, **108**: heat insulator, **110**: gas supply line, **112**: gate valve, **114**: gas exhaust line, **116**: container, **120**: heating furnace, **122**: container, **124**: container, **130**: heating furnace, **132**: conveyor belt, **134**: container, **140**: heating furnace, **142**: material input port, **144**: atmosphere control portion, **146**: collecting portion, **200**: active material layer, **201**: graphene compound, **211a**: positive electrode, **211b**: negative electrode, **212a**: lead, **212b**: lead, **214**: separator, **215a**: bonding portion, **215b**: bonding portion, **217**: fixing member, **250**: battery, **251**: exterior body, **261**: folded portion, **262**: seal portion, **263**: seal portion, **271**: crest line, **272**: trough line, **273**: space, **300**: secondary battery, **301**: positive electrode can, **302**: negative electrode can, **303**: gasket, **304**: positive electrode, **305**: positive electrode current collector, **306**: positive electrode active material layer, **307**: negative electrode, **308**: negative electrode current collector, **309**: negative electrode active material layer, **310**: separator, **500**: secondary battery, **501**: positive electrode current collector, **502**: positive electrode active material layer, **503**: positive electrode, **504**: negative electrode current collector, **505**: negative electrode active material layer, **506**: negative electrode, **507**: separator, **508**: electrolyte solution, **509**: exterior body, **510**: positive electrode lead electrode, **511**: negative electrode lead electrode, **600**: secondary battery, **601**: positive electrode cap, **602**: battery can, **603**: positive electrode terminal, **604**: positive electrode, **605**: separator, **606**: negative electrode, **607**: negative electrode terminal, **608**: insulating plate, **609**: insulating plate, **611**: PTC element, **612**: safety valve mechanism, **613**: conductive plate, **614**: conductive plate, **615**: module, **616**: conducting wiring, **617**: temperature control device, **900**: circuit board, **902**: mixture, **902-3**: mixture, **903**: mixture, **903-2**: mixture, **903-3**: mixture, **904**: positive electrode active material, **904-2**: positive electrode active material, **904-3**: positive electrode active material, **904-4**: positive electrode active material, **905**: mixture, **906**: fluoride, **908**: mixture, **909**: mixture, **910**: label, **911**: terminal, **912**: circuit, **913**: secondary battery, **914**: antenna, **915**: antenna, **916**: layer, **917**: layer, **918**: antenna, **919**: terminal, **920**: display device, **921**: sensor, **922**: terminal, **930**: housing, **930a**: housing, **930b**: housing, **931**: negative electrode, **932**: positive electrode, **933**: separator, **950**: wound body, **951**: terminal, **952**: terminal, **980**: secondary battery, **981**: film, **982**: film, **993**: wound body, **994**: negative electrode, **995**: positive electrode, **996**: separator, **997**: lead electrode, **998**: lead electrode, **7100**: portable display device, **7101**: housing, **7102**: display portion, **7103**: operation button, **7104**: secondary battery, **7200**: portable information terminal, **7201**: housing, **7202**: display portion, **7203**: band, **7204**: buckle, **7205**: operation button, **7206**: input output terminal, **7207**: icon, **7300**: display device, **7304**: display portion, **7400**: mobile phone, **7401**: housing, **7402**: display portion, **7403**: operation button, **7404**: external connection port, **7405**: speaker, **7406**: microphone, **7407**: secondary battery, **8000**: display device, **8001**: housing, **8002**: display portion, **8003**: speaker portion, **8004**: secondary battery, **8021**: charging apparatus, **8022**: cable, **8024**: secondary battery, **8100**: lighting device, **8101**: housing, **8102**: light source, **8103**: secondary battery, **8104**: ceiling, **8105**: sidewall, **8106**: floor, **8107**: window, **8200**: indoor unit, **8201**: housing, **8202**: air outlet, **8203**: secondary battery, **8204**: outdoor unit, **8300**: electric refrigerator-freezer, **8301**: housing, **8302**: refrigerator door, **8303**: freezer door, **8304**: secondary battery, **8400**: automobile, **8401**: headlight, **8406**: electric motor, **8500**: automobile, **8600**: motor scooter, **8601**: side mirror, **8602**: secondary battery, **8603**: indicator, **8604**: storage unit under seat, **9600**: tablet terminal, **9625**: switch, **9626**: switch, **9627**: power switch, **9628**: operation switch, **9629**: fastener, **9630**: housing, **9630a**: housing, **9630b**: housing, **9631**: display portion, **9633**: solar cell, **9634**: charge and discharge control circuit, **9635**: power storage unit, **9636**: DC-DC converter, **9637**: converter, **9640**: movable portion

Claims

1. A method for forming a positive electrode active material, wherein a first container that includes a mixture of lithium cobalt oxide, a first fluoride, and a magnesium compound and a second fluoride that is outside the first container are provided in a heating furnace, and the heating furnace is heated at a temperature higher than or equal to a temperature at which at least one of the first fluoride or the second fluoride is volatilized or sublimated, wherein the first fluoride and the magnesium compound are different.
 2. The method for forming a positive electrode active material according to claim 1, wherein the first fluoride is lithium fluoride and the second fluoride is lithium fluoride.
 3. The method for forming a positive electrode active material according to claim 2, wherein the heating furnace is heated at higher than or equal to 730° C. and lower than or equal to 1130° C.
 4. The method for forming a positive electrode active material according to claim 1, wherein the magnesium compound is magnesium fluoride.
 5. The method for forming a positive electrode active material according to claim 1, wherein the heating furnace is heated after an atmosphere in the heating furnace is replaced with oxygen.
 6. A method for forming a positive electrode active material, wherein a first container that contains a mixture of lithium cobalt oxide, a first fluoride, and a magnesium compound and a second container that includes a second fluoride are provided in a heating furnace, and the heating furnace is heated at a temperature higher than or equal to a temperature at which at least one of the first fluoride or the second fluoride is volatilized or sublimated, wherein the first fluoride and the magnesium compound are different.
 7. The method for forming a positive electrode active material according to claim 6, wherein the first fluoride is lithium fluoride and the second fluoride is lithium fluoride.
 8. The method for forming a positive electrode active material according to claim 7, wherein the heating furnace is heated at higher than or equal to 730° C. and lower than or equal to 1130° C.
 9. The method for forming a positive electrode active material according to claim 6, wherein the magnesium compound is magnesium fluoride.
-