

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250282022

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Bubel; Simon et al.

Two Component Chemical Mechanical Polishing

Abstract

Systems and methods for polishing semiconductor workpieces are provided. In one example, the polishing system includes a platen operable to rotate about an axis. The polishing system further includes a polishing pad on the platen. The polishing system further includes a workpiece carrier operable to bring a semiconductor workpiece into contact with the polishing pad. The polishing pad includes a first zone and a second zone.

Inventors: Bubel; Simon (Carrboro, NC), Karunaratne; Dinusha Priyadarshani (Cary, NC)

Applicant: Wolfspeed, Inc. (Durham, NC)

Family ID: 1000007739286

Appl. No.: 18/598804

Filed: March 07, 2024

Publication Classification

Int. Cl.: B24B37/26 (20120101); B24B37/005 (20120101); B24B37/22 (20120101); B24B37/24 (20120101); B24B57/02 (20060101)

U.S. Cl.:

CPC B24B37/26 (20130101); B24B37/005 (20130101); B24B37/245 (20130101); B24B57/02 (20130101); B24B37/22 (20130101)

Background/Summary

FIELD

[0001] The present disclosure relates generally to semiconductor workpieces and fabrication

processes for semiconductor workpieces, such as semiconductor wafers used in semiconductor device fabrication.

BACKGROUND

[0002] Power semiconductor devices may carry large currents and support high voltages. A wide variety of power semiconductor devices are known in the art including, for example, transistors, diodes, thyristors, power modules, discrete power semiconductor packages, and other devices. For instance, example semiconductor devices may be transistor devices such as Metal Oxide Semiconductor Field Effect Transistors (“MOSFET”), bipolar junction transistors (“BJTs”), Insulated Gate Bipolar Transistors (“IGBT”), Gate Turn-Off Transistors (“GTO”), junction field effect transistors (“JFET”), high electron mobility transistors (“HEMT”) and other devices. Example semiconductor devices may be diodes, such as Schottky diodes or other devices. Example semiconductor devices may be power modules, which may include one or more power devices and other circuit components and can be used, for instance, to dynamically switch large amounts of power through various components, such as motors, inverters, generators, and the like. These semiconductor devices may be fabricated from wide bandgap semiconductor materials, such as silicon carbide (“SiC”) and/or Group III nitride-based semiconductor materials. The fabrication process may require processing of wide bandgap semiconductor wafers, such as silicon carbide semiconductor wafers.

SUMMARY

[0003] Aspects and advantages of embodiments of the present disclosure will be set forth in part in the following description, or may be learned from the description, or may be learned through practice of the embodiments.

[0004] One example aspect of the present disclosure is directed to a polishing system for a semiconductor workpiece. The polishing system includes a platen operable to rotate about an axis. The polishing system further includes a polishing pad on the platen. The polishing system further includes a workpiece carrier operable to bring a semiconductor workpiece into contact with the polishing pad. The polishing pad comprises a first zone and a second zone.

[0005] Another example aspect of the present disclosure is directed to a polishing system for a semiconductor workpiece. The polishing system includes a platen operable to rotate about an axis. The polishing system further includes a polishing pad on the platen. The polishing system further includes a workpiece carrier operable to bring a semiconductor workpiece into contact with the polishing pad. The polishing system further includes a controller configured to control an actuator to perform operations. The operations include activating an oxidation process on the semiconductor workpiece for a first process period. The operations further include activating an oxide removal process on the semiconductor workpiece for a second process period.

[0006] Another example aspect of the present disclosure is directed to a method for polishing a surface of a workpiece. The method includes providing a surface of a workpiece on a polishing pad. The method further includes imparting relative motion between the polishing and the workpiece. The method further includes providing an oxidizing material to the polishing pad. The method further includes providing an oxide removal material to the polishing pad in a time separated manner or a spatially separated manner relative to providing the oxidizing material to the polishing pad.

[0007] Another example aspect of the present disclosure is directed to a method of polishing a workpiece. The method includes providing a surface of a workpiece on a polishing pad. The method further includes imparting relative motion between the polishing pad and the workpiece. The method further includes providing an actuatable material to the polishing pad. The method further includes activating the actuatable material in a pulsed manner to provide a time separation between a first process and a second process on the workpiece.

[0008] These and other features, aspects and advantages of various embodiments will become better understood with reference to the following description and appended claims. The

accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate embodiments of the present disclosure and, together with the description, explain the related principles.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] Detailed discussion of embodiments directed to one of ordinary skill in the art are set forth in the specification, which refers to the appended figures, in which:

[0010] FIG. 1 depicts an example polishing system for a semiconductor workpiece according to example embodiments of the present disclosure;

[0011] FIG. 2 depicts a top-down view of the platen, polishing pad, and semiconductor wafer on a polishing system according to example aspects of the present disclosure;

[0012] FIG. 3 depicts a cross-sectional view of an example polishing pad with a separator according to example embodiments of the present disclosure;

[0013] FIG. 4 depicts a cross-sectional view of an example polishing pad with a separator according to example embodiments of the present disclosure;

[0014] FIG. 5 depicts an example polishing system for a semiconductor workpiece according to example embodiments of the present disclosure;

[0015] FIGS. 6A, 6B, and 6C depict example polishing systems for a semiconductor workpiece according to example embodiments of the present disclosure.

[0016] FIG. 7 depicts a flow chart of an example method according to example embodiments of the present disclosure;

[0017] FIG. 8 depicts a flow chart of an example method according to example embodiments of the present disclosure.

DETAILED DESCRIPTION

[0018] Reference now will be made in detail to embodiments, one or more examples of which are illustrated in the drawings. Each example is provided by way of explanation of the embodiments, not limitation of the present disclosure. In fact, it will be apparent to those skilled in the art that various modifications and variations can be made to the embodiments without departing from the scope or spirit of the present disclosure. For instance, features illustrated or described as part of one embodiment can be used with another embodiment to yield a still further embodiment. Thus, it is intended that aspects of the present disclosure cover such modifications and variations.

[0019] Power semiconductor devices are often fabricated from wide bandgap semiconductor materials, such as silicon carbide or Group III-nitride based semiconductor materials (e.g., gallium nitride). Herein, a wide bandgap semiconductor material refers to a semiconductor material having a bandgap greater than 1.40 eV. Aspects of the present disclosure are discussed with reference to silicon carbide-based semiconductor structures as wide bandgap semiconductor structures. Those of ordinary skill in the art, using the disclosures provided herein, will understand that example embodiments of the present disclosure may be used with any semiconductor material, such as other wide bandgap semiconductor materials, without deviating from the scope of the present disclosure. Example wide bandgap semiconductor materials include silicon carbide and the Group III-nitrides.

[0020] Power semiconductor devices may be fabricated using epitaxial layers formed on a semiconductor workpiece, such as a silicon carbide semiconductor wafer. Power semiconductor device fabrication processes may include surface processing operations that are performed on the silicon carbide semiconductor wafer to prepare one or more surfaces of the silicon carbide semiconductor wafer for later processing steps, such as surface implantation, formation of epitaxial layers, metallization, etc. Example surface processing operations may include grinding operations, lapping operations, and polishing operations.

[0021] Aspects of the present disclosure are discussed with reference to a semiconductor workpiece that is a semiconductor wafer that includes silicon carbide (“silicon carbide semiconductor wafer”) for purposes of illustration and discussion. Those of ordinary skill in the art, using the disclosures provided herein, will understand that aspects of the present disclosure can be used with other semiconductor workpieces. Other semiconductor workpieces may include carrier substrates, ingots, boules, polycrystalline substrates, monocrystalline substrates, bulk materials having a thickness of greater than 1 mm, such as greater than about 5 mm, such as greater than about 10 mm, such as greater than about 20 mm, such as greater than about 50 mm, such as greater than about 100 mm, to 200 mm, etc.

[0022] Grinding is a material removal process that is used to remove material from the semiconductor wafer. Grinding may be used to reduce a thickness of a semiconductor wafer. Grinding typically involves exposing the semiconductor wafer to an abrasive containing surface, such as grind teeth on a grind wheel. Grinding may remove material of the semiconductor wafer through engagement with the abrasive surface.

[0023] Lapping is a precision finishing process that uses a loose abrasive in slurry form. The slurry typically includes coarser particles (e.g., largest dimension of the particles being greater than about 100 microns) to remove material from the semiconductor wafer. Lapping typically does not include engaging the semiconductor wafer with an abrasive-containing surface on the lapping tool (e.g., a wheel or disc having an abrasive-containing surface). Instead, the semiconductor wafer typically comes into contact with a lapping plate or a tile usually made of metal. Lapping typically provides better planarization of the semiconductor wafer relative to grinding.

[0024] Polishing is a process to remove imperfections and create a smooth surface with a low surface roughness. Polishing may be performed using a slurry and a polishing pad. The slurry typically includes finer particles relative to lapping, but coarser particles relative to chemical mechanical planarization (CMP). Polishing typically provides better planarization of the semiconductor wafer relative to grinding.

[0025] CMP is a type of fine or ultrafine polishing, typically used to produce a smoother surface ready, for instance, for epitaxial growth of layers on the semiconductor wafer. CMP may be performed chemically and/or mechanically to remove imperfections and to create a smooth and flat surface with low surface roughness. CMP typically involves changing the material of the semiconductor through a chemical process (e.g., oxidation) and removing the new material from the semiconductor wafer through abrasive contact with a slurry and/or other abrasive surface or polishing pad (e.g., oxide removal). In CMP, the abrasive elements in the slurry typically remove the product of the chemical process and do not remove the bulk material of the semiconductor wafer, often leaving reduced subsurface damage.

[0026] Polishing tools (e.g., such as chemical mechanical polishing (CMP) tools) may be used after grinding operations to polish and/or smooth a semiconductor wafer surface. Polishing tools, such as CMP tools, may use a combination of chemical and mechanical forces to remove excess materials from a wafer surface, ensuring desired flatness and smoothness. Polishing tools, such as CMP tools, may include a rotating platen, polishing pad, and a slurry containing abrasive particles and chemical agents. As the wafer is pressed against the polishing pad and rotated, the slurry chemically reacts with and/or mechanically removes material, resulting in a highly planar and smooth surface.

[0027] Grinding and polishing silicon carbide semiconductor wafers may pose several challenges due to the inherent properties of the material. Silicon carbide is an extremely hard and brittle compound with a prominent level of abrasiveness, making the polishing process more demanding. One challenge is the potential for excessive tool wear and heat generation during grinding or polishing, which can affect the quality of the finished product. The hardness of silicon carbide may also lead to the formation of cracks or fractures if not properly managed, impacting the structural integrity of the material. Additionally, achieving precise dimensions and surface finishes can be

challenging due to the resistance of silicon carbide to abrasion. Controlling parameters such as polishing pad selection, rotational speed, slurry composition, and/or cooling mechanisms may be important to overcoming these challenges and ensuring the successful fabrication of silicon carbide components with the desired properties and performance.

[0028] Some systems and methods for polishing wafers may pose several challenges unique to polishing processes. For instance, polishing semiconductor wafers may require performing several different polishing processes on the semiconductor wafer in an alternating fashion. For instance, certain polishing processes may include an oxidation process followed by an oxide removal process. The oxidation process may form a thin oxide layer to aid in planarization of the semiconductor wafer surface. The oxide removal process may use one or more abrasives (e.g., as part of the slurry and/or the polishing pad) and/or oxide removal chemistry to remove the oxide layer from the semiconductor wafer surface during the polishing process to smooth the surface of the semiconductor wafer.

[0029] For instance, in some examples, a slurry used during the polishing process may need to be effective as an oxidizing material for silicon carbide but at the same time, needs to be effective in stabilizing the oxide removal process. If the oxide removal process is using an abrasive particle, the properties of a slurry designed for oxidation may limit the possible chemistry of abrasive particles. At the same time, using abrasive particles in the slurry requires a stabilizing or dispersion agent which again, may not be selected to increase slurry stability but rather to be compatible with the oxidizing properties of the slurry. Even in nominally abrasive-free slurries (e.g., potassium permanganate slurries), manganese oxide may be formed, which acts as an abrasive particle and may be difficult to control (e.g., prevents the re-use of the slurry through filtration as manganese oxide may be formed in all possible sizes). In addition to the difficulty in combining good oxidizing action and particle dispersion simultaneously, it may be difficult to employ other additives or chemicals that effectively dissolve the oxide formed during oxidation. In addition, in some examples, the abrasive elements in a slurry may coagulate or precipitate, leading to tool contamination, clogging, or workpiece scratching via larger abrasive agglomerates.

[0030] Accordingly, example aspects of the present disclosure are directed to polishing tools (e.g., CMP tools) that are adapted to implement one or more polishing processes on a silicon carbide wafer. For instance, a polishing system may include a CMP tool including a platen with a polishing pad for polishing silicon carbide semiconductor wafers and a workpiece carrier to bring a surface of a silicon carbide semiconductor wafer against the polishing pad on the platen. The platen with the polishing pad may be operable to rotate about an axis. The platen and/or the polishing pad may include multiple zones with each zone being associated with its own process. For example, the platen and/or polishing pad may include a first zone associated with a first process and a second zone associated with a second process. The first process may be, for instance, an oxidation process, an anodization process, electrochemical oxidation process, or other process. The second process may be, for instance, an oxide removal process, a reduction process, or other process.

[0031] Aspects of the present disclosure are discussed with reference to an oxidation process as a first process and an oxide removal process as a second process. Those of ordinary skill in the art, using the disclosures provided herein, will understand that aspects of the present disclosure may implement other processes, such as anodization processes, electrochemical processes, reductions processes, etc., without deviating from the scope of the present disclosure.

[0032] In some instances, an oxidizing material may be deposited on and/or otherwise provided on the polishing pad in the first zone of the polishing pad. For instance, in some embodiments, the oxidizing material may be a part of or integrated into the polishing pad. Similarly, in some instances, an oxide removal material and/or abrasive containing material may be deposited on and/or otherwise provided on the polishing pad in the second zone of the platen. For instance, in some embodiments, the oxidize removal material may be a part of or integrated into the polishing pad.

[0033] In some examples, the platen may include a separator that divides the platen into two or more zones. For example, the platen may include a separator that divides the platen and/or the polishing pad into a first zone and a second zone. The separator may come in a variety of forms. For instance, the separator may be a fluid blade operable to inject a separator fluid away from the platen creating separated regions or zones on the platen. The separator fluid may be, for example, air, water, liquid, gas, or any other fluid capable of maintaining separation between different zones on the platen. In some examples, the fluid is a neutralizing substance that may be used, for instance, to reduce undesirable reactions. In some embodiments, the separator may include a lip that protrudes from the platen. The lip may be made of, for instance, polymer, silicon, rubber, or plastic. The separator may be distributed across the platen in a variety of ways. For instance, the separator may pass through the center of the platen and may divide the platen into equal or into unequal portions. Further, in some instances, the separator may create a first zone with a different size relative to the second zone.

[0034] The polishing system may include a delivery system (e.g., slurry delivery system) that may deposit one or more materials (e.g., a slurry and/or oxidizing agents, oxide removal agents, etc.) onto the platen. In some embodiments, the delivery system may be operable to deliver an oxidizing material or oxidizing agents (e.g., with the slurry or separate from the slurry) to a first zone of the polishing pad and an oxide removal material (e.g., with the slurry or separate from the slurry) to a second zone of the polishing pad. In some examples, the oxidizing agent may include, for instance, one or more of hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxymonosulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate. In some examples, the oxidizing agent may include an organic peroxide, such as one or more of benzoyl peroxide or dimethyl peroxide. In some examples, the oxidizing agent includes hydrogen peroxide that may or may not be exposed to one or more Fe^{+2} compounds. In some examples the oxidizing agent (e.g., hydrogen peroxide) may include additional chemical elements to improve their oxidizing properties, such as NaHCO_3 and/or KHCO_3 . In some examples, the oxide removal material may include one or more abrasive elements (e.g., abrasive particles), for instance, provided as part of a slurry. In some examples, the oxide removal material may include one or more etchants for etching an oxide, such as acid-based etchants (with or without a buffer), such as fluorine containing etchants (e.g., hydrofluoric acid, fluoroantimonic acid, ammonium bifluoride), caustic compounds (e.g., sodium hydroxide and/or potassium hydroxide), or other etchants.

[0035] In some examples, the polishing system may additionally include a controller configured to operate the polishing system. For instance, the controller may control a delivery system within the polishing system based, at least in part, on a position of a first zone on the polishing pad and a second zone on the polishing pad. For example, the controller may control the delivery system to deposit one or more materials on the platen based on the location of the first zone or second zone relative to the delivery system. For instance, the delivery system may provide oxidizing materials to the first zone of the polishing pad when the polishing pad passes under a delivery outlet associated with delivery of the oxidizing materials. The delivery system may be controlled to provide oxide removal materials to the second zone of the polishing pad when the polishing pad passes under a delivery outlet associated with delivery of oxide removal materials.

[0036] In some embodiments, the controller may be configured to control an actuator that may alternate polishing processes for one or more-time intervals. For instance, the actuator may activate an oxidation process on the workpiece for a first process period and then activate an oxide removal process on the workpiece for a second process period. In some instances, there may be no time overlap between the first process period and the second process period. However, in some instances, the first process period and the second process period may be separated by a time interval.

[0037] In some examples, the oxidizing material and/or the oxide removal material may include an

actuatable material that is activated by an external stimulus (e.g., the actuator). For instance, the actuatable material may include a material that is activated by one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator (e.g., heat source, laser, lamp), or plasma-based actuator (e.g., the actuator). For instance, in some embodiments, the material may be inert and not react with a surface of the polishing platen and/or the silicon carbide semiconductor wafer until the material is actuated by the actuator. In some embodiments, the material may be activated to react with the silicon carbide semiconductor wafer only when exposed (or not exposed) to the external stimulus from the actuator. In this way, the active properties of the additive may be controlled (e.g., pulsed) by controlling the actuator. [0038] In some examples, the additive may be activated when it interacts (e.g., mixes, contacts, etc.) other additives or components in the grinding system. For instance, the additive may interact with other additives already present on the semiconductor wafer and/or the polishing pad to activate properties of the additive.

[0039] In some instances, the actuator may control the delivery system of the polishing system and may instruct the delivery system to deliver one or more materials to the polishing pad. For example, the actuator may control the delivery system to deliver an oxidizing material to a surface of the platen during a first process period and to deliver an oxide removal material to the surface of the platen during the second process period. In some embodiments, the controller may control the delivery system to deliver an actuatable material to the platen. The actuator may then activate the actuatable material on the platen to provide oxidation to the platen during a first process period. Similarly, the actuator may also activate the actuatable material on the platen to provide oxide removal to the platen during a second process period.

[0040] Aspects of the present disclosure provide a number of technical effects and benefits. For instance, use of a polishing platen and/or polishing pads with multiple zones may reduce wear and consumable cost of the platens and/or polishing pads themselves. As previously mentioned, traditional methods of polishing may lead to platen contamination between polishing processes and therefore rapidly wear the polishing pads on the platen. Therefore, separating the platen and/or polishing pad into one or more zones with dedicated materials and processes for each allows for reduced or eliminated contamination between polishing processes thereby enhancing polishing pad lifespan.

[0041] Contamination between multiple polishing processes may reduce the effectiveness of each respective process thereby requiring longer process periods for each process to achieve the desired results. Keeping the materials of each polishing process separate eliminates contamination between polishing processes improving the effectiveness of each process and thereby reducing the duration of process periods. Additional benefits from embodiments of the present disclosure may also include improved system stability due to reduced clogging and, therefore, reduced cleaning efforts required for wafer polishing systems.

[0042] Additionally, by keeping the materials of individual polishing processes separated into isolated zones, the efficiency of each process may be improved. For instance, separating the materials (e.g., oxide materials and oxide removal materials) into separate zones may allow for optimizing process conditions for each part of a polishing process separately, increasing the overall efficiency of the polishing process. For instance, by optimizing the oxidizing function in a first zone or a first time period, a slurry with the need to carry abrasive particles during an oxidizing process may no longer be needed. Thus, the issue of clogging through slurry instabilities may be solved. The oxide removal process in a second zone or a second time period may be free to use a process with abrasive particles tailored for oxide removal only that may not cause clogging or workpiece scratching through agglomerates.

[0043] It will be understood that, although the terms first, second, etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another. For example, a first element could be termed a

second element, and, similarly, a second element could be termed a first element, without departing from the scope of the present disclosure. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

[0044] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises” “comprising,” “includes” and/or “including” when used herein, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

[0045] Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms used herein should be interpreted as having a meaning that is consistent with their meaning in the context of this specification and the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

[0046] It will be understood that when an element such as a layer, structure, region, or substrate is referred to as being “on” or extending “onto” another element, it may be directly on or extend directly onto the other element or intervening elements may also be present and may be only partially on the other element. In contrast, when an element is referred to as being “directly on” or extending “directly onto” another element, there are no intervening elements present, and may be partially directly on the other element. It will also be understood that when an element is referred to as being “connected” or “coupled” to another element, it may be directly connected or coupled to the other element or intervening elements may be present. In contrast, when an element is referred to as being “directly connected” or “directly coupled” to another element, there are no intervening elements present.

[0047] As used herein, a first structure “at least partially overlaps” or is “overlapping” a second structure if an axis that is perpendicular to a major surface of the first structure passes through both the first structure and the second structure. A “peripheral portion” of a structure includes regions of a structure that are closer to a perimeter of a surface of the structure relative to a geometric center of the surface of the structure. A “center portion” of the structure includes regions of the structure that are closer to a geometric center of the surface of the structure relative to a perimeter of the surface. “Generally perpendicular” means within 15 degrees of perpendicular. “Generally parallel” means within 15 degrees of parallel.

[0048] Relative terms such as “below” or “above” or “upper” or “lower” or “horizontal” or “lateral” or “vertical” may be used herein to describe a relationship of one element, layer or region to another element, layer or region as illustrated in the figures. It will be understood that these terms are intended to encompass different orientations of the device in addition to the orientation depicted in the figures.

[0049] Embodiments of the disclosure are described herein with reference to cross-section illustrations that are schematic illustrations of idealized embodiments (and intermediate structures) of the invention. The thickness of layers and regions in the drawings may be exaggerated for clarity. Additionally, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments of the invention should not be construed as limited to the particular shapes of regions illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. Similarly, it will be understood that variations in the dimensions are to be expected based on standard deviations in manufacturing procedures. As used herein, “approximately” or “about” includes values within 10% of the nominal value.

[0050] Like numbers refer to like elements throughout. Thus, the same or similar numbers may be

described with reference to other drawings even if they are neither mentioned nor described in the corresponding drawing. Also, elements that are not denoted by reference numbers may be described with reference to other drawings.

[0051] Some embodiments of the invention are described with reference to semiconductor layers and/or regions which are characterized as having a conductivity type such as n type or p type, which refers to the majority carrier concentration in the layer and/or region. Thus, n type material has a majority equilibrium concentration of negatively charged electrons, while p type material has a majority equilibrium concentration of positively charged holes. Some material may be designated with a “+” or “-” (as in n+, n-, p+, p-, n++, n-, p++, p--, or the like), to indicate a relatively larger (“+”) or smaller (“-”) concentration of majority carriers compared to another layer or region. However, such notation does not imply the existence of a particular concentration of majority or minority carriers in a layer or region.

[0052] In the drawings and specification, there have been disclosed typical embodiments and, although specific terms are employed, they are used in a generic and descriptive sense only and not for purposes of limitation of the scope set forth in the following claims.

[0053] FIG. 1 depicts an example polishing system **100** for a silicon carbide semiconductor wafer **105** according to example embodiments of the present disclosure. The polishing system **100** is a CMP system operable to perform one or more polishing operations for a silicon carbide wafer **105**. The silicon carbide wafer **105** may include 4H silicon carbide, 6H silicon carbide or other crystal structure. The silicon carbide wafer **105** may be doped or undoped. In some examples, the polishing system **100** includes a platen **110** with a polishing pad **120**, a workpiece carrier **130**, a delivery system **140**, a conditioning head **150**, and a controller **160**.

[0054] More specifically, the polishing system **100** includes the platen **110**. The platen **110** may be operable to rotate about an axis **104**. The platen **110** may be operable to rotate about the axis **104** in either a clockwise or counterclockwise direction. In some examples, the platen **110** may rotate, for instance, at a rotational speed in a range of about 10 rpm to about 10000 rpm, such as about 10 rpm to about 7500 rpm, such as about 10 rpm to about 2000 rpm, such as about 10 rpm to about 1000 rpm, such as about 10 rpm to about 500 rpm, such as about 10 rpm to about 120 rpm.

[0055] The platen **110** may include a receptacle **112**. The receptacle **112** may be configured to hold a polishing pad **120** for a CMP process. The receptacle **112** may be a surface configured to support or receive the polishing pad **120**. In some examples, the receptacle **112** may be a planar surface that supports the polishing pad **120**.

[0056] The polishing pad **120** may provide a surface for polishing the silicon carbide semiconductor wafer **105**. The polishing pad **120** may include durable and chemically resistant materials such as polyurethane and/or polyether ether ketone (PEEK) material. The polishing pad **120** may have a surface with a specified roughness and porosity to facilitate polishing a silicon carbide semiconductor wafer **105**. The polishing pad **120** may have one or more wear-resistant layers (e.g., diamond layers, diamond-like carbon layers, ceramic layers, etc.). The polishing pad **120** may include grooves or dimples to increase slurry distribution and reduce edge effects during the CMP process. The polishing pad **120** may include a cushioning layer (e.g., foam or rubber), in some examples, to facilitate adaptation of the polishing pad **120** to the topography of the semiconductor wafer **105**, providing improved planarity of the semiconductor wafer **105**.

[0057] The polishing pad **120** may have a diameter. The diameter may be greater than a size of the silicon carbide semiconductor wafer **105**. The polishing pad **120** may have a diameter in a range of, for instance, about 150 mm to about 820 mm, such as in a range of about 150 mm to about 400 mm, such as in a range of about 150 mm to about 300 mm. In some examples, the diameter of the polishing pad **120** may be smaller or nearly the same size as the diameter of the platen **110** (FIG. 1). However, the diameter of the polishing pad **120** may be larger than the diameter of the platen **110** without deviating from the scope of the present disclosure. In some examples, the polishing pad **120** may have a thickness in a range of about 2 mm to about 40 mm, such as in a range 5 mm

to about 40 mm, such as in a range of about 10 mm to about 40 mm.

[0058] According to examples aspects of the present disclosure, the platen **110** and/or polishing pad **120** may additionally include a separator **115** operable to separate the polishing pad **120** into two or more zones or regions. As used herein, the terms “zone” and “region” on the polishing pad may be used interchangeably. In some examples, the polishing pad **120** may be separated into a first zone **122** and a second zone **124** by the separator **115**. In some embodiments, two separate polishing pads are used, one for the first zone **122** and one for the second zone **124**. In some examples, the same polishing pad **120** is divided into zones using a separator **115**. FIG. 1 depicts two regions (e.g., first region **122** and second region **124**) for purposes of illustration and discussion. Those of ordinary skill in the art, using the disclosures provided herein, will understand that more regions (e.g., three or more, such as four more, such as five or more) may be included without deviating from the scope of the present disclosure.

[0059] FIG. 2 depicts a plan view of the platen **110**, polishing pad **120**, and semiconductor wafer **105** on the polishing system **100** according to example aspects of the present disclosure. The platen **110** may include the separator **115** which may divide the polishing pad **120** into two or more zones. For example, the polishing pad **120** may be divided into a first zone **122** and a second zone **124**. As depicted in FIG. 2, the separator **115** may pass through the center of the polishing pad **120**, but it should be appreciated the separator may divide the platen **110** and/or polishing pad **120** into a variety of different quantity and size zones. For example, the separator may divide the platen **110** and/or polishing pad such that the first zone **122** is a different size relative to the second zone **124**. However, other suitable divisions and/or additional zones may be used without deviating from the scope of the present disclosure.

[0060] The polishing pad **120** in the first zone **122** may have the same or a different material configuration relative to the polishing pad **120** in the second zone **124**. For instance, in some examples, the second zone **124** of the polishing pad **120** may include more abrasive containing materials relative to the first zone **122**, or vice versa. In some examples, the first zone **122** may include a material (e.g., an additive) associated with a first process. The second zone **124** may include a material (e.g., an additive) associated with a second process.

[0061] For instance, in some examples, the first zone **122** may include one or more oxidizing materials embedded in or provided on the first zone **122**. The oxidizing material may be provided as a liquid or power on the first zone **122**. In some examples, the oxidizing material may include, for instance, one or more hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxydisulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate. In some examples, the oxidizing material may include an organic peroxide, such as one or more of benzoyl peroxide or dimethyl peroxide. In some examples, the oxidizing material includes hydrogen peroxide that may or may not be exposed to one or more Fe.sup.+2 compounds. In some examples, the oxidizing material (e.g., hydrogen peroxide) may include additional chemical elements to improve their oxidizing properties, such as NaHCO.sub.3 and/or KHCO.sub.3.

[0062] In some embodiments, the second zone **124** may include one or more oxide removal material embedded in or provided on the second zone **124**. For instance, the polishing pad may include an abrasive surface. The abrasive surface may include an abrasive containing material. The abrasive containing material may be suitable for grinding silicon carbide. The abrasive containing material may include a plurality of abrasive elements (e.g., abrasive particles) in a host material or matrix. In some examples, the host material may include one or more vitreous material, metal, resin, and/or other sintered material and/or organic material. In some embodiments, the abrasive elements may be diamond or a diamond coated material. In some embodiments, the abrasive elements may include a ceramic material. Example ceramic materials may include, for instance, boron carbide (B.sub.4C) and cubic boron nitride (BN). In some examples, the abrasive elements may include one or more metal oxides (sintered and/or unsintered). In some embodiments, the

abrasive elements may include silica, ceria, zirconia, alumina, silicon carbide, nitrates, and/or other carbides and in general one or more of: (i) diamond; (ii) ceramic; (iii) metal nitride; (iv) metal oxide, (v) metal carbide; (vi) metalloid nitride; (vii) metalloid oxide; (viii) metalloid carbide; (ix) carbon group nitride; (x) carbon group oxide; or (xi) carbon group carbide.

[0063] The second zone **124** may include one or more additives for oxide removal, such one or more etchants, such as acid-based etchants (with or without a buffer), such as fluorine containing etchants (e.g., hydrofluoric acid, fluoroantimonic acid, ammonium bifluoride), caustic compounds (e.g., sodium hydroxide and/or potassium hydroxide), or other etchants.

[0064] FIG. **3** depicts a cross-sectional view of a polishing pad **120** with a separator **115** according to example embodiments of the present disclosure. In the example of FIG. **3**, the separator **115** includes a lip **116** that extends and/or protrudes from the platen **110** and/or the polishing pad **120**. The lip **116** may be made from a variety of materials, for example, polymer, silicone, rubber, and/or plastic. The lip **116** may separate the polishing pad **120** into the first zone **122** and the second zone **124**.

[0065] FIG. **4** depicts a cross-sectional view of a polishing pad **120** with a separator **116** according to example embodiments of the present disclosure. In the example of FIG. **4**, the separator **116** includes a fluid blade **118** (e.g., an air blade) operable to provide a separator fluid **119** to separate the first region **122** from the second region **124**. The separator fluid **119** may be, for example, air, water, liquid, or a gas, or other fluid. The separator fluid **119** may separate the polishing pad **120** into the first zone **122** and the second zone **124**. In some examples, the separator fluid **119** is a neutralizing substance that may be used, for instance, to reduce undesirable reactions.

[0066] Referring back to FIG. **1**, the first zone **122** may be associated with a first process and the second zone **124** may be associated with a second process. The second process may be different from the first process. For instance, when the semiconductor wafer **105** is provided against the first zone **122**, the semiconductor wafer **105** may be subjected to a first process (e.g., an oxidation process). When the semiconductor wafer **105** is provided against the second zone **124**, the semiconductor wafer **105** may be subjected to a second process (e.g., an oxide removal process). In this way, the first process may be implemented in a spatially separated manner relative to the second process.

[0067] As an example, the first process may be an oxidation process. The second process may be an oxide removal process. The first zone **122** may be associated with exposing the semiconductor wafer **105** to an oxidizing material (e.g., with or without a slurry). The second zone **124** may be associated with an oxide removal process. The second zone may be associated with exposing the semiconductor wafer **105** to an oxide removal material (e.g., with or without a slurry), such as one or more abrasive elements.

[0068] In some examples, the polishing system **100** includes a delivery system **140**. The delivery system **140** may be used to deliver a slurry to the polishing pad **120** held on the platen **110** during a CMP process, for instance, from a slurry delivery outlet **142**. In some examples, the slurry may be, for instance, a permanganate-based slurry, such as potassium permanganate-based slurry. Other suitable slurries with one or more abrasive elements (e.g., abrasive particles) may be used without deviating from the scope of the present disclosure. The delivery system **140** may further include one or more fluid delivery outlets **144**. The fluid delivery outlets **144** may be configured to provide one or more fluids (e.g., coolant, additive, lubricant, etc.) to the polishing pad **120** during a polishing process. In some examples, the delivery system **140** may include an additive delivery system **145** configured to deliver one or more additives (e.g., oxidizing material, oxide removal material) either with the slurry through the slurry delivery outlet **142** or separate from the slurry through the fluid delivery outlet **144**.

[0069] Aspects of the present disclosure are discussed with reference to providing the oxidizing materials and oxide removal materials to the polishing pad **120** through fluid delivery outlets **144** for purposes of illustration and discussion. Those of ordinary skill in the art, using the disclosures

provided herein, will understand that the delivery system **140** may deliver materials (e.g., slurry, oxidizing materials, oxide removal materials) to the polishing pad **120** in various ways without deviating from the scope of the present disclosure, such as from a plurality of fluid delivery outlets, from apertures in the platen and/or the polishing pad, or from other fluid delivery techniques.

[0070] In some examples, the polishing system **100** includes a workpiece carrier **130**. The workpiece carrier **130** is operable to bring one or more silicon carbide semiconductor wafers **105** into contact with the polishing pad **120** to implement a polishing process. In some examples, the workpiece carrier **130** may be operable to hold a single silicon carbide semiconductor wafer **105** for single wafer processing. In some examples, the workpiece carrier **130** may be operable to hold a plurality of silicon carbide semiconductor wafers **105** for batch processing.

[0071] The workpiece carrier **130** may be operable to rotate the silicon carbide semiconductor wafer **105** about an axis **132**. The axis **132** is not aligned with the axis **104** associated with the platen **110**. The workpiece carrier **130** may be operable to rotate the silicon carbide semiconductor wafer **105** about the axis **132** in either a clockwise or counterclockwise direction. In some examples, the workpiece carrier **130** may rotate, for instance, at a rotational speed in range of about 10 rpm to about 10000 rpm, such as about 10 rpm to about 7500 rpm, such as about 10 rpm to about 2000 rpm, such as about 10 rpm to about 1000 rpm, such as about 10 rpm to about 500 rpm, such as about 10 rpm to about 120 rpm. The workpiece carrier **130** may rotate in the same direction as the platen **110** or in a different direction relative to the platen **110**.

[0072] The workpiece carrier **130** may be able to provide a downforce **134** of the silicon carbide semiconductor wafer **105** against the polishing pad **120**. The downforce **134** of the workpiece carrier **130** may be controlled to adjust the polishing rate of the polishing process of the silicon carbide semiconductor wafer **105**.

[0073] The workpiece carrier **130** may also oscillate in a lateral direction along the surface of the polishing pad **120**. This will allow exposure of the semiconductor wafer **105** to different portions of the polishing pad **120** (e.g., at different radii of the polishing pad **120**) during a polishing operation.

[0074] The polishing system **100** may include a conditioning head **150**. The conditioning head **150** may rotate about an axis **152**, such that the conditioning head **150** rotates along the surface of the polishing pad **120** (e.g., in either a clockwise or counterclockwise direction). In some examples, the conditioning head **150** may be on a swing arm **154** that may swing about an axis **156** to move the conditioning head **150** to different locations on the polishing pad **120**. The conditioning head **1500** may include an abrasive-containing material that is used to condition or dress the polishing pad **120** as the polishing pad **120** is subject to glazing during a polishing process.

[0075] The system **100** includes one or more control devices, such as a controller **160**. The controller **160** may include one or more processors **162** and one or more memory devices **164**. The one or more memory devices **164** may store computer-readable instructions that when executed by the one or more processors **162** cause the one or more processors **162** to perform one or more control functions, such as any of the functions described herein. The controller **160** may be in communication with various other aspects of the system **100** through one or more wired and/or wireless control links. For instance, the controller **160** may control the platen **110**, the workpiece carrier **130**, the delivery system **140**, and/or the conditioning head **150** to implement polishing processes according to examples of the present disclosure.

[0076] For instance, in some examples, the controller **160** may control the delivery system **140** to deliver a first material to the first zone **122** of the polishing pad **120** and to deliver a second material to the second zone **124** of the polishing pad **120**. For instance, the controller **160** may control the delivery system **140** to provide an oxidizing material to the first zone of the polishing pad **120** (e.g., through one or more of slurry delivery outlet **142** and/or fluid delivery outlet **144**) and to provide an oxide removal material to the second zone **124** of the polishing pad **120** (e.g., through one or more of slurry delivery outlet **142** and/or fluid delivery outlet **144**).

[0077] For instance, in some examples, the controller **160** may be operable to control the delivery

system **140** based at least in part on a position of the first zone **122** and the second zone **124** (e.g., based on a rotational position of the polishing pad **120**). For instance, in some examples, the controller **160** may control the delivery system **140** to provide oxidizing materials to the first zone **122** of the polishing pad **120** when the polishing pad **120** passes under a delivery outlet (e.g., slurry delivery outlet **142** and/or fluid delivery outlet **144**) associated with delivery of the oxidizing materials. The controller **160** may control the delivery system **140** to provide oxide removal materials to the second zone **124** of the polishing pad **120** when the polishing pad **120** passes under a delivery outlet (e.g., slurry delivery outlet **142** and/or fluid delivery outlet **144**) associated with delivery of oxide removal materials. In this way, the controller **160** may control the delivery system **140** to provide the oxide removal materials in a spatially separated manner relative to providing to the oxidizing materials to the polishing pad **120**.

[0078] In some examples, the controller **160** may control the delivery system **140** to provide a first material (e.g., oxidizing material) to the polishing pad **120** and a second material (e.g., oxide removal material) in a time-separated manner. For instance, the controller **160** may control the delivery system **140** as an actuator to provide to provide a first material (e.g., oxidizing material) to a surface of the polishing pad **120** during the first process period and to provide an oxide removal material to the surface of the polishing pad **120** during the second process period. There may be no time overlap between the first process period and the second process period. For instance, the first process period may be separated from the second process period by a time interval.

[0079] As shown in FIG. **1**, in some examples, the system **100** may include an actuator **170**. The actuator **170** may be, for instance, one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator (e.g., heat source, laser, lamp), or plasma-based actuator. The actuator **170** may be configured to provide an external stimulus to an actuatable material on the polishing pad **120** to activate properties of the actuatable material. The actuatable material may be provided to the polishing pad **120** through, for instance, the delivery system **140** or through other suitable techniques, such as through apertures in the polishing pad **120**. In some examples, the actuatable material is embedded in or otherwise on the polishing pad **120**.

[0080] In some examples, the actuatable material may act as an oxidizing material based on the external stimulus from the actuator **170**. In some examples, the actuatable material may act as an oxide remove material based on the external stimulus from the actuator **170**. For instance, the actuatable material may include a material that is activated by the actuator **170**. For instance, in some embodiments, the material may be inert and not react with a surface of the silicon carbide semiconductor wafer until the material is actuated by the actuator **170**. In some embodiments, the material may be activated to react with the silicon carbide semiconductor wafer only when exposed (or not exposed) to the external stimulus from the actuator **170**. In this way, the active properties of the actuatable material may be controlled (e.g., pulsed) by controlling the actuator **170**. For instance, the controller **160** may control the actuator **170** to activate the actuatable material in a pulsed manner to provide a time separation between a first process and a second process on the semiconductor wafer **105**.

[0081] As one example, the controller **160** may be configured to control the actuator **170** to activate oxidation properties of the actuatable material to provide oxidation during a first process period. The actuator **170** may be controlled not to activate oxidation in the actuatable material during a second process period during which oxide removal may occur using an oxide removal material. As another example, the controller **160** may be configured to control the actuator **170** to activate oxide removable properties of the actuatable material to provide oxide removal during a first process period. The actuator **170** may be controlled not to activate oxide removal during the second process period during which oxidation may occur using an oxidizing material.

[0082] In some examples, the controller **160** may be configured to control the actuator **170** to activate a first actuatable material to act as an oxidizing material during a first process period. The

controller **160** may be configured to control the actuator **170** to activate a second actuatable material to act as an oxide removal material during a second process period. In this way, the controller **160** may be configured to pulse or otherwise control the actuator **170** to provide oxidation and oxide removal in a time separated manner.

[0083] In some examples, for instance, an ultraviolet actuator may provide UV light stimulus to provide photochemical activation and/or photocatalytic effects in an actuatable material, such as hydrogen peroxide and/or organic peroxide to generate, for instance, hydroxyl radicals for oxidation of the semiconductor wafer.

[0084] FIG. 5 depicts a polishing system **200** according to example embodiments of the present disclosure. The polishing system **200** is similar to the polishing system **100** of FIG. 1. However, the polishing system **200** does not include a polishing pad with spatial separation of a first zone **122** and a second zone **124** as described with reference to FIG. 1. Rather, the polishing pad **220** of FIG. 5 has a polishing pad with a single zone with no separator.

[0085] The polishing system **200** may include a controller **160** operable to control the fluid delivery system **140** and/or the actuator **170** to provide a first process and a second process in a time separated manner (but not necessarily in a spatially separated manner). For instance, in some examples, the controller **160** may control the delivery system **140** to provide a first material (e.g., oxidizing material) to the polishing pad **220** and a second material (e.g., oxide removal material) in a time-separated manner. For instance, the controller **160** may control the delivery system **140** as an actuator to provide to provide a first material (e.g., oxidating material) to a surface of the polishing pad **220** during the first process period and to provide an oxide removal material to the surface of the polishing pad **220** during the second process period. There may be no time overlap between the first process period and the second process period. For instance, the first process period may be separated from the second process period by a time interval.

[0086] The system **200** may include an actuator **170**. The actuator **170** may be, for instance, one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator (e.g., heat source, laser, lamp), or plasma-based actuator. The actuator **170** may be configured to provide an external stimulus to an actuatable material on the polishing pad **220** to activate properties of the actuatable material. The actuatable material may be provided to the polishing pad **220** through, for instance, the delivery system **140** or through other suitable techniques, such as through apertures in the polishing pad **220**. In some examples, the actuatable material is embedded in or otherwise on the polishing pad **220**.

[0087] In some examples, the actuatable material may act as an oxidizing material based on the external stimulus from the actuator **170**. In some examples, the actuatable material may act as an oxide removal material based on the external stimulus from the actuator **170**.

[0088] For instance, in some examples, the material may be inert and not react with a surface of the silicon carbide semiconductor wafer until the material is actuated by the actuator **170**. In some embodiments, the material may be activated to react with the silicon carbide semiconductor wafer only when exposed (or not exposed) to the external stimulus from the actuator **170**. In this way, the active properties of the actuatable material may be controlled (e.g., pulsed) by controlling the actuator **170**. For instance, the controller **160** may control the actuator **170** to activate the actuatable material in a pulsed manner to provide a time separation between a first process and a second process on the semiconductor wafer **105**.

[0089] As one example, the controller **160** may be configured to control the actuator **170** to activate oxidation properties of the actuatable material to provide oxidation during a first process period. The actuator **170** may be controlled not to activate oxidation in the actuatable material during a second process period during which oxide removal may occur using an oxide removal material. As another example, the controller **160** may be configured to control the actuator **170** to activate oxide removable properties of the actuatable material to provide oxide removal during a first process period. The actuator **170** may be controlled not to activate oxide removal during the second process

period during which oxidation may occur using an oxidizing material.

[0090] In some examples, the controller **160** may be configured to control the actuator **170** to activate a first actuatable material to act as an oxidizing material during a first process period. The controller **160** may be configured to control the actuator **170** to activate a second actuatable material to act as an oxide removal material during a second process period. In this way, the controller **160** may be configured to pulse or otherwise control the actuator **170** to provide oxidation and oxide removal in a time separated manner. There may be no time overlap between the first process period and the second process period. For instance, the first process period may be separated from the second process period by a time interval.

[0091] In some examples, the first process (e.g., oxidation process) and the second process (e.g., oxide removal process) may be spatially separated and/or time separated by implementing the first process and the second process using different polishing pads, different polishing systems and/or different process platforms. For instance, the first process may be performed on a first polishing pad and a second process may be performed on a second polishing pad. As another example, the first process may be performed on a polishing pad and the second process may be performed in a separate process platform (e.g., that is not a polishing system). As another example, the first process may be performed in a separate process platform (e.g., that is not a polishing system) and the second process may be performed on a polishing pad.

[0092] For instance, FIG. **6A** depicts an example polishing system **300** according to examples of the present disclosure. As illustrated, the system **300** includes a first polishing pad system **310** and a second polishing pad system **320**. The first polishing pad system **310** may be used to implement a first process (e.g., oxidation process) for a first process period. The second polishing pad system **320** may be used to implement a second process (e.g., oxide removal process) for a second process period.

[0093] The first polishing pad system **310** may include one or more components similar to the system **200** illustrated in FIG. **5**, such as a platen, polishing pad, workpiece carrier, delivery system, controller, actuator, etc. The first polishing pad system **310** may be configured to implement, for instance, an oxidation process as described with reference to FIGS. **1** and **5**.

[0094] The second polishing pad system **320** may include one or more components similar to the system **200** illustrated in FIG. **5**, such as a platen, polishing pad, workpiece carrier, delivery system, controller, actuator, etc. The second polishing pad system **320** may be configured to implement, for instance, an oxide removal process as described with reference to FIGS. **1** and **5**.

[0095] In some examples, the first polishing pad system **310** and the second polishing pad system **320** may share some common components. For instance, in some examples, a common workpiece carrier **330** may provide a semiconductor wafer against a polishing pad of the first polishing pad system **310** for a first process period and provide the semiconductor wafer against a polishing pad of the second polishing pad system **320** for a second process period. However, in other embodiments, each of the first polishing pad system **310** and the second polishing pad system **320** may have a separate workpiece carrier. In some examples, a common controller may control aspects of the first polishing pad system **310** and the second polishing pad system **320**.

[0096] FIG. **6B** depicts an example polishing system **350** according to example embodiments of the present disclosure. As illustrated, the system **350** includes a first polishing pad system **310** and a second process platform **340**. The first polishing pad system **310** may be used to implement a first process (e.g., oxidation process) for a first process period. The second process platform **340** may be used to implement a second process (e.g., oxide removal process) for a second process period.

[0097] The first polishing pad system **310** may include one or more components similar to the system **200** illustrated in FIG. **5**, such as a platen, polishing pad, workpiece carrier, delivery system, controller, actuator, etc. The first polishing pad system **310** may be configured to implement, for instance, an oxidation process as described with reference to FIGS. **1** and **5**. The first polishing pad system **310** may include a polishing pad, for instance, configured to perform the first process, such

as an oxidation process. The delivery system for the first polishing pad system **320** may be operable to deliver an oxidizing material.

[0098] The second process platform **340** may be a different type of tool used to implement the second process (e.g., oxide removal process). For instance, the second process platform may include one or more of an etchant bath, wet etch system, dry etch system, for other system that may be used to implement the second process (e.g., oxide removal process). Those of ordinary skill in the art, using the disclosures provided herein, will understand that a variety of different process platforms may be used to implement the second process (e.g., oxide removal process) without deviating from the scope of the present disclosure.

[0099] FIG. **6C** depicts an example polishing system **370** according to example embodiments of the present disclosure. As illustrated, the system **370** includes a first process platform **360** and a second polishing pad system **320**. The first process platform **360** may be used to implement a first process (e.g., oxidation process) for a first process period. The second polishing pad system **320** may be used to implement a second process (e.g., oxide removal process) for a second process period.

[0100] The second polishing pad system **320** may include one or more components similar to the system **200** illustrated in FIG. **5**, such as a platen, polishing pad, workpiece carrier, delivery system, controller, actuator, etc. The second polishing pad system **320** may include a polishing pad, for instance, configured to perform the second process, such as an oxide removal process. The delivery system for the second polishing pad system **320** may be operable to deliver an oxide removal material.

[0101] The first process platform **360** may be a different type of tool relative to the second polishing pad system **320**. The first process platform **360** may be configured to implement the first process (e.g., oxidation process). For instance, the first process platform may include one or more baths, deposition systems, oxidation systems, etc. configured to implement the first process. Those of ordinary skill in the art, using the disclosures provided herein, will understand that a variety of different process platforms may be used to implement the first process (e.g., oxidation process) without deviating from the scope of the present disclosure.

[0102] FIG. **7** depicts a flow chart of an example method **600** according to example embodiments of the present disclosure. The method **600** may be implemented, for instance, using the polishing system **100** of FIG. **1**. The method **600** depicts operations performed in a particular order for purposes of illustration and discussion. Those of ordinary skill in the art, using the disclosures provided herein, will understand that the operations of any of the methods described herein may be adapted, expanded, performed simultaneously, omitted, rearranged, include steps not illustrated, and/or modified in various ways without deviating from the scope of the present disclosure.

[0103] At **610**, the method **600** may include providing a surface of a workpiece on a polishing pad. For instance, a workpiece may be on a workpiece support and the workpiece may be operable to provide a surface of the workpiece to the polishing pad. In some embodiments, the polishing pad may be on a platen of a chemical mechanical polishing (CMP) system.

[0104] At **620**, the method **600** may include imparting relative motion between the platen and the workpiece. For instance, the platen may be rotated about a first axis causing relative motion between the polishing pad and the workpiece. In some embodiments, the workpiece may be rotated about a second axis imparting relative motion between the polishing pad and the workpiece. In some examples, the second axis may be different from the first axis.

[0105] At **630**, the method **600** may include providing an oxide material to the polishing pad. Additionally, at **640**, the method **600** may include providing an oxide removal material to the polishing pad in a time separated manner or a spatially separated manner relative to providing the oxidizing material to the platen.

[0106] In some embodiments, providing the oxidizing material and the oxide removal material in a spatially separated manner includes providing the oxidizing material and oxide removal material to separate the first and second zones on the platen. The first and second zones may be separated on

the polishing pad by a separator such as, for example, a fluid blade or polymer lip. The separator may pass through the center of the polishing pad, and, in some instances, the separator may create a first zone that is a different size relative to the second zone. In examples including a fluid blade, the fluid blade may be operable to inject a separator fluid such as, for example, air, water, liquid, or gas, to separate the first zone from the second zone. In some embodiments, the separator may include a lip that protrudes from the platen and/or the polishing pad. The lip may comprise, for example, polymer, silicon, rubber, or plastic.

[0107] In some embodiments, the oxidizing material and the oxide removal material are provided in a time-separated manner. For instance, the oxidizing material may be provided to the polishing pad for a first process period, and the oxide removal material may be provided to the platen for a second process period. In some instances, there may be no time overlap between the first process period and the second process period. In some embodiments, the first process period and the second process period may be separated by a time interval.

[0108] In some examples, the oxidizing material may include, for instance, one or more of hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxydisulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate. In some examples, the oxidizing material may include an organic peroxide, such as one or more of benzoyl peroxide or dimethyl peroxide. In some examples, the oxidizing material includes hydrogen peroxide that may or may not be exposed to one or more Fe.sup.+2 compounds. In some examples, the oxidizing material (e.g., hydrogen peroxide) may include additional chemical elements to improve their oxidizing properties, such as NaHCO.sub.3 and/or KHCO.sub.3.

[0109] In some examples, the oxide removal material may include one or more abrasive elements (e.g., abrasive particles), for instance, provided as part of a slurry. In some examples, the oxide removal material may include one or more etchants for etching an oxide, such as acid-based etchants (with or without a buffer), such as fluorine containing etchants (e.g., hydrofluoric acid, fluoroantimonic acid, ammonium bifluoride), caustic compounds (e.g., sodium hydroxide and/or potassium hydroxide), or other etchants.

[0110] The oxidizing material and the oxide removal material may be provided on the polishing pad in a variety of ways without deviating from the scope of the present disclosure. For instance, in some embodiments, the oxidizing material and/or the oxide removal material may be provided via a fluid through one or more apertures through the polishing pad. Additionally, or alternatively, the oxidizing material and/or the oxide removal material may be provided via a fluid through a fluid delivery outlet. Additionally, or alternatively, the oxidizing material and/or the oxide removal material may be embedded as part of the polishing pad.

[0111] FIG. 8 depicts a flow chart of an example method **700** according to example embodiments of the present disclosure. The method **700** may be implemented, for instance, using the polishing system **100** of FIG. 1 or the polishing system **200** of FIG. 5. The method **700** depicts operations performed in a particular order for purposes of illustration and discussion. Those of ordinary skill in the art, using the disclosures provided herein, will understand that the operations of any of the methods described herein may be adapted, expanded, performed simultaneously, omitted, rearranged, include steps not illustrated, and/or modified in various ways without deviating from the scope of the present disclosure.

[0112] At **710**, the method **700** may include providing a surface of a workpiece on a polishing pad. For instance, a workpiece may be provided on a carrier and the workpiece carrier may be operable to provide a surface of the workpiece to the platen. In some instances, the platen may be a part of a chemical mechanical polishing (CMP) system.

[0113] At **720**, the method **700** may include imparting relative motion between the platen and the workpiece. For instance, the polishing pad may be rotated about a first axis. The workpiece may be rotated about a second axis. In some examples, the second axis may be different and not aligned

with the first axis.

[0114] At **730**, the method **700** may include providing an actuatable material to the polishing pad. The actuatable material may be provided on the polishing pad in a variety of ways without deviating from the scope of the present disclosure. For instance, in some embodiments, the actuatable material may be provided via a fluid through one or more apertures through the polishing pad. Additionally, or alternatively, the actuatable material may be provided via a fluid through a fluid delivery outlet. Additionally, or alternatively, the actuatable material may be embedded as part of the polishing pad.

[0115] At **740**, the method **700** may include activating the actuatable material in a pulsed manner to provide a time separation between an oxidation process and an oxide removal process. More particularly, the actuatable material may be activated by an external stimulus from an actuator. For instance, the actuatable material may be activated by one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator (e.g., heat source, laser, lamp), or plasma-based actuator (e.g., the actuator).

[0116] For instance, in some embodiments, the actuatable material may be inert and not react with a surface of the polishing platen and/or the silicon carbide semiconductor wafer until the material is actuated by the actuator. In some embodiments, the material may be activated to react with the surface of the silicon carbide semiconductor wafer only when exposed (or not exposed) to the external stimulus from the actuator. In this way, the active properties of the additive may be controlled (e.g., pulsed) by controlling the actuator.

[0117] For instance, the actuator may be pulsed to selectively activate the actuatable material and, for example, provide the oxidation process on the workpiece. Additionally, or alternatively, the actuator may be pulsed to selectively activate the actuatable material to provide the oxide removal process on the workpiece. The actuator may include a variety of components. As examples, the actuator may include one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator (e.g., heat source, laser, lamp), or plasma-based actuator.

[0118] One example aspect of the present disclosure is directed to a polishing system for a semiconductor workpiece. The polishing system includes a platen operable to rotate about an axis. The polishing system further includes a polishing pad on the platen. The polishing system further includes a workpiece carrier operable to bring a semiconductor workpiece into contact with the polishing pad. The polishing pad comprises a first zone and a second zone.

[0119] In some examples, the first zone and the second zone are separated by a separator.

[0120] In some examples, the separator comprises a fluid blade operable to inject a separator fluid to separate the first zone from the second zone.

[0121] In some examples, the separator fluid comprises air, water, liquid, or a gas.

[0122] In some examples, the separator comprises a lip that protrudes from the polishing pad.

[0123] In some examples, the lip comprises a polymer.

[0124] In some examples, the separator passes through a center of the polishing pad.

[0125] In some examples, the first zone is a different size relative to the second zone.

[0126] In some examples, the grinding system for a semiconductor workpiece may further include a delivery system operable to deliver an oxidizing material to the first zone and an oxide removal material to the second zone.

[0127] In some examples, the oxidizing material comprises hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxydisulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate.

[0128] In some examples, the oxide removal material comprises one or more of abrasive elements provided as part of a slurry.

[0129] In some examples, the polishing system comprises a controller operable to control the

delivery system based at least in part on a position of the first zone and the second zone.

[0130] In some examples, the first zone comprises an oxidizing material on the polishing pad in the first zone.

[0131] In some examples, the second zone comprises one or more abrasive elements, wherein the one or more abrasive elements comprise one or more of: (i) diamond; (ii) ceramic; (iii) metal nitride; (iv) metal oxide, (v) metal carbide; (vi) metalloid nitride; (vii) metalloid oxide; (viii) metalloid carbide; (ix) carbon group nitride; (x) carbon group oxide; or (xi) carbon group carbide.

[0132] In some examples, the delivery system comprises one or more fluid delivery outlets operable to deliver a fluid to a surface of the polishing pad.

[0133] In some examples, the workpiece carrier is operable to rotate the semiconductor workpiece about a second axis.

[0134] In some examples, the polishing system comprises a chemical mechanical polishing (CMP) system.

[0135] Another example aspect of the present disclosure is directed to a polishing system for a semiconductor workpiece. The polishing system includes a platen operable to rotate about an axis. The polishing system further includes a polishing pad on the platen. The polishing system further includes a workpiece carrier operable to bring a semiconductor workpiece into contact with the polishing pad. The polishing system further includes a controller configured to control an actuator to perform operations. The operations include activating an oxidation process on the semiconductor workpiece for a first process period. The operations further include activating an oxide removal process on the semiconductor workpiece for a second process period.

[0136] In some examples, there is no time overlap between the first process period and the second process period.

[0137] In some examples, the first process period and the second process period are separated by a time interval.

[0138] In some examples, the actuator comprises a delivery system, wherein the controller is configured to control the delivery system to provide an oxidizing material to a surface of the polishing pad during the first process period and to provide an oxide removal material to the surface of the polishing pad during the second process period.

[0139] In some examples, the oxidizing material comprises oxidizing material comprises hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxydisulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate.

[0140] In some examples, the oxide removal material comprises one or more of the oxide removal material comprises one or more of abrasive elements provided as part of a slurry.

[0141] In some examples, the polishing system comprises a delivery system operable to deliver an actuatable material to the polishing pad.

[0142] In some examples, the controller is configured to control the actuator to activate the actuatable material to provide oxidation during the first process period.

[0143] In some examples, the controller is configured to control the actuator to activate the actuatable material to provide oxide removal during the second process period.

[0144] In some examples, the actuator comprises one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator, or plasma-based actuator.

[0145] In some examples, the polishing system comprises a first polishing pad system and a second polishing pad system.

[0146] In some examples, the polishing system comprises a chemical mechanical polishing (CMP) system.

[0147] Another example aspect of the present disclosure is directed to a method for polishing a surface of a workpiece. The method includes providing a surface of a workpiece on a polishing

pad. The method further includes imparting relative motion between the polishing and the workpiece. The method further includes providing an oxidizing material to the polishing pad. The method further includes providing an oxide removal material to the polishing pad in a time separated manner or a spatially separated manner relative to providing the oxidizing material to the polishing pad.

[0148] In some examples, the oxidizing material and the oxide removal material are provided in a spatially separated manner.

[0149] In some examples, providing the oxidizing material and the oxide removal material in a spatially separated manner includes providing the oxidizing material to a first zone on the polishing pad; and providing the oxide removal material to a second zone on the polishing pad.

[0150] In some examples, the first zone and the second zone are separated on the polishing pad by a separator.

[0151] In some examples, the separator comprises a fluid blade operable to inject a separator fluid to separate the first zone from the second zone.

[0152] In some examples, the separator fluid comprises air, water, liquid, or a gas.

[0153] In some examples, the separator comprises a lip that protrudes from the polishing pad.

[0154] In some examples, the lip comprises a polymer.

[0155] In some examples, the separator passes through a center of the polishing pad.

[0156] In some examples, the first zone is a different size relative to the second zone.

[0157] In some examples, the oxidizing material and the oxide removal material are provided in a time-separated manner.

[0158] In some examples, providing the oxidizing material and the oxide removal material in a time separated manner includes providing the oxidizing material to the polishing pad for a first process period, and providing the oxide removal material to the polishing pad for a second process period.

[0159] In some examples, there is no time overlap between the first process period and the second process period.

[0160] In some examples, the first process period and the second process period are separated by a time interval.

[0161] In some examples, the oxidizing material comprises one or more of the oxidizing material comprises oxidizing material comprises hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxydisulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate.

[0162] In some examples, the oxide removal material comprises one or more abrasive elements provided as part of a slurry.

[0163] In some examples, providing the oxidizing material or providing the oxide removal material comprises providing a fluid through one or more apertures through the polishing pad.

[0164] In some examples, providing the oxidizing material or providing the oxide removal material comprises providing a fluid through a fluid delivery outlet.

[0165] In some examples, imparting relative motion comprises rotating the polishing pad about a first axis.

[0166] In some examples, imparting relative motion comprises rotating the workpiece about a second axis.

[0167] In some examples, imparting relative motion includes rotating the polishing pad about a first axis; and rotating the workpiece about a second axis, the second axis being different from the first axis.

[0168] In some examples, the polishing pad is part of a chemical mechanical polishing (CMP) system.

[0169] Another example aspect of the present disclosure is directed to a method of polishing a workpiece. The method includes providing a surface of a workpiece on a polishing pad. The

method further includes imparting relative motion between the polishing pad and the workpiece. The method further includes providing an actuatable material to the polishing pad. The method further includes activating the actuatable material in a pulsed manner to provide a time separation between a first process and a second process on the workpiece.

[0170] In some examples, activating the actuatable material in a pulsed manner includes pulsing an actuator to selectively activate the actuatable material.

[0171] In some examples, activating the actuatable material in a pulsed manner comprises pulsing the actuator to selectively activate the actuatable material to provide an oxidation process on the workpiece.

[0172] In some examples, activating the actuatable material in a pulsed manner comprises pulsing the actuator to selectively activate the actuatable material to provide an oxide removal process on the workpiece.

[0173] In some examples, the actuator comprises one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator, or plasma-based actuator.

[0174] In some examples, providing the actuatable material comprises providing a fluid through one or more apertures through the polishing pad.

[0175] In some examples, providing the actuatable material comprises providing a fluid through a fluid delivery outlet.

[0176] In some examples, imparting relative motion comprises rotating the polishing pad about a first axis.

[0177] In some examples, imparting relative motion comprises rotating the workpiece about a second axis.

[0178] In some examples, imparting relative motion includes rotating the polishing pad about a first axis; and rotating the workpiece about a second axis, the second axis being different from the first axis.

[0179] In some examples, the polishing pad is part of a chemical mechanical polishing (CMP) system.

[0180] While the present subject matter has been described in detail with respect to specific example embodiments thereof, it will be appreciated that those skilled in the art, upon attaining an understanding of the foregoing may readily produce alterations to, variations of, and equivalents to such embodiments. Accordingly, the scope of the present disclosure is by way of example rather than by way of limitation, and the subject disclosure does not preclude inclusion of such modifications, variations and/or additions to the present subject matter as would be readily apparent to one of ordinary skill in the art.

Claims

1. A polishing system for a semiconductor workpiece, comprising: a platen operable to rotate about an axis; a polishing pad on the platen; a workpiece carrier operable to bring a semiconductor workpiece into contact with the polishing pad; a separator fixed to the polishing pad, wherein the separator is operable to separate the polishing pad into a first zone and a second zone; and a delivery system operable to deliver an oxidizing material to the first zone and an oxide removal material to the second zone such that an oxidation process may be implemented on the workpiece in a spatially separated manner relative to an oxide removal process.

2. (canceled)

3. The polishing system of claim 1, wherein the separator comprises a fluid blade operable to inject a separator fluid to separate the first zone from the second zone.

4. The polishing system of claim 3, wherein the separator fluid comprises air, water, liquid, or a gas.

5. The polishing system of claim 1, wherein the separator comprises a lip that protrudes from the polishing pad.
6. The polishing system of claim 5, wherein the lip comprises a polymer.
7. The polishing system of claim 3, wherein the separator passes through a center of the polishing pad.
8. The polishing system of claim 1, wherein the first zone is a different size relative to the second zone.
9. (canceled)
10. The polishing system of claim 19, wherein the oxidizing material comprises hydrogen peroxide, urea peroxide, potassium hypochlorite, sodium hypochlorite, ammonium persulfate, potassium peroxymonosulfate, sodium permanganate, potassium permanganate, potassium periodate, and/or potassium persulfate.
11. The polishing system of claim 19, wherein the oxide removal material comprises one or more of abrasive elements provided as part of a slurry.
12. (canceled)
13. The polishing system of claim 1, wherein the first zone comprises an oxidizing material on the polishing pad in the first zone.
14. The polishing system of claim 1, wherein the second zone comprises one or more abrasive elements, wherein the one or more abrasive elements comprise one or more of: (i) diamond; (ii) ceramic; (iii) metal nitride; (iv) metal oxide, (v) metal carbide; (vi) metalloid nitride; (vii) metalloid oxide; (viii) metalloid carbide; (ix) carbon group nitride; (x) carbon group oxide; or (xi) carbon group carbide.
15. The polishing system of claim 1, wherein the polishing system comprises a chemical mechanical polishing (CMP) system.
16. A method for polishing a surface of a workpiece, the method comprising: providing a surface of a workpiece on a polishing pad, imparting relative motion between the polishing pad and the workpiece; during a first process period, providing an oxidizing material to the polishing pad via a fluid through one or more apertures through the polishing pad; and during a second process period, ceasing to provide the oxidizing material and providing an oxide removal material to the polishing pad.
17. (canceled)
18. The method of claim 16, wherein there is no time overlap between the first process period and the second process period.
19. A method of polishing a workpiece, the method comprising: providing a surface of a workpiece on a polishing pad; imparting relative motion between the polishing pad and the workpiece; providing an actuatable material to the polishing pad; activating the actuatable material in a pulsed manner to provide a time separation between a first process and a second process on the workpiece by pulsing an actuator to selectively activate the actuatable material while imparting relative motion between the polishing pad and the workpiece; and wherein the actuator is one or more of an electrostatic actuator, electrochemical actuator, acoustic actuator, ultrasonic actuator, optical actuator, thermal actuator, or plasma-based actuator.
20. (canceled)
21. The method of claim 19, wherein activating the actuatable material in a pulsed manner comprises pulsing the actuator to selectively activate the actuatable material to provide an oxidation process on the workpiece.
22. The method of claim 19, wherein activating the actuatable material in a pulsed manner comprises pulsing the actuator to selectively activate the actuatable material to provide an oxide removal process on the workpiece.
23. The method of claim 19, wherein providing the actuatable material comprises providing a fluid through one or more apertures through the polishing pad.

24. The method of claim 19, wherein providing the actuatable material comprises providing a fluid through a fluid delivery outlet.

25. The method of claim 19, wherein imparting relative motion comprises rotating the polishing pad about a first axis or rotating the workpiece about a second axis.
