

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12415823
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Lee; Gi-Back et al.

Heterocyclic compound and organic light-emitting device comprising same

Abstract

The present specification relates to a heterocyclic compound represented by Chemical Formula 1, and an organic light emitting device comprising the same.

Inventors:	Lee; Gi-Back (Yongin-si, KR), Heo; Yu-Jin (Yongin-si, KR), Jeong; Won-Jang (Yongin-si, KR)
Applicant:	LT MATERIALS CO., LTD. (Yongin, KR)
Family ID:	1000008818962
Assignee:	LT MATERIALS CO., LTD. (Yongin, KR)
Appl. No.:	17/612703
Filed (or PCT Filed):	October 20, 2020
PCT No.:	PCT/KR2020/014308
PCT Pub. No.:	WO2021/080282
PCT Pub. Date:	April 29, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20220289693 A1	Sep. 15, 2022

Foreign Application Priority Data

KR	10-2019-0133975	Oct. 25, 2019
----	-----------------	---------------

Publication Classification

Int. Cl.: C07F9/6521 (20060101); C07D213/16 (20060101); C07D239/26 (20060101); C07D251/24 (20060101); C07D401/10 (20060101); C07D403/10 (20060101); C07D405/10 (20060101); C07D471/04 (20060101); C07F9/32 (20060101); H10K50/15 (20230101); H10K50/16 (20230101); H10K50/17 (20230101); H10K50/18 (20230101); H10K85/60 (20230101)

U.S. Cl.:

CPC C07F9/6521 (20130101); C07D213/16 (20130101); C07D239/26 (20130101); C07D251/24 (20130101); C07D401/10 (20130101); C07D403/10 (20130101); C07D405/10 (20130101); C07D471/04 (20130101); C07F9/3229 (20130101); H10K85/622 (20230201); H10K85/624 (20230201); H10K85/654 (20230201); H10K85/6572 (20230201); H10K85/6574 (20230201); H10K50/15 (20230201); H10K50/16 (20230201); H10K50/171 (20230201); H10K50/18 (20230201)

Field of Classification Search

CPC: C07D (251/24); C07D (239/26); C07D (213/19); C07D (403/10); C07D (405/10); C07D (471/04); H01L (51/0067); H01L (51/0054); H01L (51/0072); H01L (51/0056); H01L (51/0073); H01L (51/5072); C07F (9/3229)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
4356429	12/1981	Tang	N/A	N/A
2016/0248020	12/2015	Ondari et al.	N/A	N/A
2018/0175302	12/2017	Jang et al.	N/A	N/A
2019/0207123	12/2018	Yoon et al.	N/A	N/A
2020/0168805	12/2019	Park et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
110156777	12/2018	CN	N/A
2008-231047	12/2007	JP	N/A
2015-10077	12/2014	JP	N/A
10-2015-0115848	12/2014	KR	N/A
10-2017-0065317	12/2016	KR	N/A
10-2019-0009994	12/2018	KR	N/A
10-2019-0080600	12/2018	KR	N/A
10-2019-0108935	12/2018	KR	N/A
10-2019-0108935	12/2018	KR	N/A
WO 2015/073343	12/2014	WO	N/A

OTHER PUBLICATIONS

International Search Report (PCT/ISA/210) Issued in PCT/KR2020/014308. dated Feb. 17, 2021.
cited by applicant

Kuwabara et al., "Thermally Stable Multilayered Organic Electroluminescent Devices Using Novel Starburst Molecules, 4,4',4''-Tri(N-carbazolyl)triphenylamine (TCTA) and 4,4',4''-Tris(3-methylphenylphenyl-amino)triphenylamine (m-MTDATA), as Hole-Transport Materials." Advanced Materials, vol. 6, No. 9, 1994, pp. 877-679. cited by applicant

Primary Examiner: Nguyen; Vu A

Attorney, Agent or Firm: Birch, Stewart, Kolasch & Birch, LLP

Background/Summary

TECHNICAL FIELD

(1) This application claims priority to and the benefits of Korean Patent Application No. 10-2019-0133975, filed with the Korean Intellectual Property Office on Oct. 25, 2019, the entire contents of which are incorporated herein by reference.

(2) The present specification relates to a heterocyclic compound, and an organic light emitting device comprising the same.

Background Art

(3) An organic electroluminescent device is one type of self-emissive display devices, and has an advantage of having a wide viewing angle, and a high response speed as well as having an excellent contrast.

(4) An organic light emitting device has a structure disposing an organic thin film between two electrodes. When a voltage is applied to an organic light emitting device having such a structure, electrons and holes injected from the two electrodes bind and pair in the organic thin film, and light emits as these annihilate. The organic thin film may be formed in a single layer or a multilayer as necessary.

(5) A material of the organic thin film may have a light emitting function as necessary. For example, as a material of the organic thin film, compounds capable of forming a light emitting layer themselves alone may be used, or compounds capable of performing a role of a host or a dopant of a host-dopant-based light emitting layer may also be used. In addition thereto, compounds capable of performing roles of hole injection, hole transfer, electron blocking, hole blocking, electron transfer, electron injection and the like may also be used as a material of the organic thin film.

(6) Development of an organic thin film material has been continuously required for enhancing performance, lifetime or efficiency of an organic light emitting device.

PRIOR ART DOCUMENTS

Documents

(7) U.S. Pat. No. 4,356,429

DISCLOSURE

Technical Problem

(8) The present disclosure is directed to providing a heterocyclic compound, and an organic light emitting device comprising the same.

Technical Solution

(9) One embodiment of the present application provides a heterocyclic compound represented by the following Chemical Formula 1.

(10) ##STR00001##

(11) In Chemical Formula 1,

(12) R1 and R2 are the same as or different from each other, and each independently a substituted

or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group, or groups adjacent to each other bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring,

(13) L1 is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group,

(14) X1 to X3 are the same as or different from each other, and each independently N; or CRa, and at least one thereof is N,

(15) Ra, Ar2 and Ar4 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R''; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group, or two or more groups adjacent to each other bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring,

(16) R3 to R11 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; deuterium; a halogen group; —CN; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R''; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group, or two or more groups adjacent to each other bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring,

(17) R, R' and R'' are the same as or different from each other, and each independently hydrogen; a substituted or unsubstituted C1 to C40 alkyl group; or a substituted or unsubstituted C6 to C40 aryl group, and

(18) m is an integer of 1 to 6, and when m is 2 or greater, substituents in the parentheses are the same as or different from each other.

(19) Another embodiment of the present application provides an organic light emitting device comprising a first electrode; a second electrode provided opposite to the first electrode; and one or more organic material layers provided between the first electrode and the second electrode, wherein one or more layers of the organic material layers comprise the heterocyclic compound represented by Chemical Formula 1.

Advantageous Effects

(20) A compound described in the present specification can be used as a material of an organic material layer of an organic light emitting device. In the organic light emitting device, the compound is capable of performing a role of a hole injection material, a hole transfer material, a hole blocking material, a light emitting material, an electron transfer material, an electron injection material, a charge generation material or the like. Particularly, the compound can be used as an electron transfer layer material or a hole blocking layer material of the organic light emitting device.

(21) When using the compound represented by Chemical Formula 1 in the organic material layer, a driving voltage of the device can be lowered, light efficiency can be enhanced, and lifetime properties of the device can be enhanced by thermal stability of the compound.

(22) In other words, the compound represented by Chemical Formula 1 has an azine-based substituent having excellent electron transfer properties at a specific position on the skeleton having a fluorene group, and when included in an organic light emitting device, superior efficiency and driving are obtained through adjusting band gap and T1 value by strengthening electron

withdrawing properties.

(23) Particularly, when using the azine derivative as an electron transfer layer, superior electron withdrawing properties of the azine functional group improves the flow of electrons enhancing electron transfer capability of the electron transfer layer, and by combining the azine moiety with a substituent with enhanced hole properties, planarity of the azine derivative and the glass transition temperature increase, which increases thermal stability of the compound.

(24) In addition, electron transfer capability and hole blocking capability can be enhanced through adjusting band gap and T1 value, and molecular stability increases as well, and as a result, the device can have lowered driving voltage, enhanced light efficiency, and lifetime properties of the device can be enhanced due to thermal stability of the compound.

Description

DESCRIPTION OF DRAWINGS

(1) FIG. 1 to FIG. 4 are diagrams each schematically illustrating a lamination structure of an organic light emitting device according to one embodiment of the present application.

REFERENCE NUMERAL

(2) **100**: Substrate **200**: Anode **300**: Organic Material Layer **301**: Hole Injection Layer **302**: Hole Transfer Layer **303**: Light Emitting Layer **304**: Hole Blocking Layer **305**: Electron Transfer Layer **306**: Electron Injection Layer **400**: Cathode

MODE FOR DISCLOSURE

(3) Hereinafter, the present application will be described in detail.

(4) In the present specification, a “case of a substituent being not indicated in a chemical formula or compound structure” means that a hydrogen atom bonds to a carbon atom. However, since deuterium (²H) is an isotope of hydrogen, some hydrogen atoms may be deuterium.

(5) In one embodiment of the present application, a “case of a substituent being not indicated in a chemical formula or compound structure” may mean that positions that may come as a substituent may all be hydrogen or deuterium. In other words, since deuterium is an isotope of hydrogen, some hydrogen atoms may be deuterium that is an isotope, and herein, a content of the deuterium may be from 0% to 100%.

(6) In one embodiment of the present application, in a “case of a substituent being not indicated in a chemical formula or compound structure”, hydrogen and deuterium may be mixed in compounds when deuterium is not explicitly excluded such as a deuterium content being 0% or a hydrogen content being 100%. In other words, an expression of “substituent X is hydrogen” does not exclude deuterium such as a hydrogen content being 100% or a deuterium content being 0%, and therefore, may mean a state in which hydrogen and deuterium are mixed.

(7) In one embodiment of the present application, deuterium is one of isotopes of hydrogen, is an element having deuteron formed with one proton and one neutron as a nucleus, and may be expressed as hydrogen-2, and the elemental symbol may also be written as D or ²H.

(8) In one embodiment of the present application, an isotope means an atom with the same atomic number (Z) but with a different mass number (A), and may also be interpreted as an element with the same number of protons but with a different number of neutrons.

(9) In one embodiment of the present application, a meaning of a content T % of a specific substituent may be defined as $T2/T1 \times 100 = T \%$ when the total number of substituents that a basic compound may have is defined as T1, and the number of specific substituents among these is defined as T2.

(10) In other words, in one example, having a deuterium content of 20% in a phenyl group represented by

(11) ##STR00002##

means that the total number of substituents that the phenyl group may have is 5 (T1 in the formula), and the number of deuterium among these is 1 (T2 in the formula). In other words, having a deuterium content of 20% in a phenyl group may be represented by the following structural formulae.

(12) ##STR00003##

(13) In addition, in one embodiment of the present application, “a phenyl group having a deuterium content of 0%” may mean a phenyl group that does not comprise a deuterium atom, that is, a phenyl group that has 5 hydrogen atoms.

(14) In the present specification, the term “substitution” means a hydrogen atom bonding to a carbon atom of a compound being changed to another substituent, and the position of substitution is not limited as long as it is a position at which the hydrogen atom is substituted, that is, a position at which a substituent can substitute, and when two or more substituents substitute, the two or more substituents may be the same as or different from each other.

(15) In the present specification, “substituted or unsubstituted” means being substituted with one or more substituents selected from the group consisting of C1 to C60 linear or branched alkyl; C2 to C60 linear or branched alkenyl; C2 to C60 linear or branched alkynyl; C3 to C60 monocyclic or polycyclic cycloalkyl; C2 to C60 monocyclic or polycyclic heterocycloalkyl; C6 to C60 monocyclic or polycyclic aryl; C2 to C60 monocyclic or polycyclic heteroaryl; —SiRR'R"; —P(=O)RR'; C1 to C20 alkylamine; C6 to C60 monocyclic or polycyclic arylamine; and C2 to C60 monocyclic or polycyclic heteroarylamine, or being unsubstituted, or being substituted with a substituent linking two or more substituents selected from among the substituents illustrated above, or being unsubstituted.

(16) In the present specification, the halogen may be fluorine, chlorine, bromine or iodine.

(17) In the present specification, the alkyl group comprises linear or branched having 1 to 60 carbon atoms, and may be further substituted with other substituents. The number of carbon atoms of the alkyl group may be from 1 to 60, specifically from 1 to 40 and more specifically from 1 to 20. Specific examples thereof may comprise a methyl group, an ethyl group, a propyl group, an n-propyl group, an isopropyl group, a butyl group, an n-butyl group, an isobutyl group, a tert-butyl group, a sec-butyl group, a 1-methyl-butyl group, a 1-ethylbutyl group, a pentyl group, an n-pentyl group, an isopentyl group, a neopentyl group, a tert-pentyl group, a hexyl group, an n-hexyl group, a 1-methylpentyl group, a 2-methylpentyl group, a 4-methyl-2-pentyl group, a 3,3-dimethylbutyl group, a 2-ethylbutyl group, a heptyl group, an n-heptyl group, a 1-methylhexyl group, a cyclopentylmethyl group, a cyclohexylmethyl group, an octyl group, an n-octyl group, a tert-octyl group, a 1-methylheptyl group, a 2-ethylhexyl group, a 2-propylpentyl group, an n-nonyl group, a 2,2-dimethylheptyl group, a 1-ethyl-propyl group, a 1,1-dimethyl-propyl group, an isohexyl group, a 2-methylpentyl group, a 4-methylhexyl group, a 5-methylhexyl group and the like, but are not limited thereto.

(18) In the present specification, the alkenyl group comprises linear or branched having 2 to 60 carbon atoms, and may be further substituted with other substituents. The number of carbon atoms of the alkenyl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 2 to 20. Specific examples thereof may comprise a vinyl group, a 1-propenyl group, an isopropenyl group, a 1-butenyl group, a 2-butenyl group, a 3-butenyl group, a 1-pentenyl group, a 2-pentenyl group, a 3-pentenyl group, a 3-methyl-1-butenyl group, a 1,3-butadienyl group, an allyl group, a 1-phenylvinyl-1-yl group, a 2-phenylvinyl-1-yl group, a 2,2-diphenylvinyl-1-yl group, a 2-phenyl-2-(naphthyl-1-yl)vinyl-1-yl group, a 2,2-bis(diphenyl-1-yl)vinyl-1-yl group, a stilbenyl group, a styrenyl group and the like, but are not limited thereto.

(19) In the present specification, the alkynyl group comprises linear or branched having 2 to 60 carbon atoms, and may be further substituted with other substituents. The number of carbon atoms of the alkynyl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 2 to 20.

(20) In the present specification, the alkoxy group may be linear, branched or cyclic. The number of carbon atoms of the alkoxy group is not particularly limited, but is preferably from 1 to 20. Specific examples thereof may comprise methoxy, ethoxy, n-propoxy, isopropoxy, i-propyloxy, n-butoxy, isobutoxy, tert-butoxy, sec-butoxy, n-pentyloxy, neopentyloxy, isopentyloxy, n-hexyloxy, 3,3-dimethylbutyloxy, 2-ethylbutyloxy, n-octyloxy, n-nonyloxy, n-decyloxy, benzyloxy, p-methylbenzyloxy and the like, but are not limited thereto.

(21) In the present specification, the cycloalkyl group comprises monocyclic or polycyclic having 3 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the cycloalkyl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be a cycloalkyl group, but may also be different types of cyclic groups such as a heterocycloalkyl group, an aryl group and a heteroaryl group. The number of carbon groups of the cycloalkyl group may be from 3 to 60, specifically from 3 to 40 and more specifically from 5 to 20. Specific examples thereof may comprise a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a 3-methylcyclopentyl group, a 2,3-dimethylcyclopentyl group, a cyclohexyl group, a 3-methylcyclohexyl group, a 4-methylcyclohexyl group, a 2,3-dimethylcyclohexyl group, a 3,4,5-trimethylcyclohexyl group, a 4-tert-butylcyclohexyl group, a cycloheptyl group, a cyclooctyl group and the like, but are not limited thereto.

(22) In the present specification, the heterocycloalkyl group comprises O, S, Se, N or Si as a heteroatom, comprises monocyclic or polycyclic having 2 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the heterocycloalkyl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be a heterocycloalkyl group, but may also be different types of cyclic groups such as a cycloalkyl group, an aryl group and a heteroaryl group. The number of carbon atoms of the heterocycloalkyl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 3 to 20.

(23) In the present specification, the aryl group comprises monocyclic or polycyclic having 6 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the aryl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be an aryl group, but may also be different types of cyclic groups such as a cycloalkyl group, a heterocycloalkyl group and a heteroaryl group. The aryl group comprises a Spiro group. The number of carbon atoms of the aryl group may be from 6 to 60, specifically from 6 to 40 and more specifically from 6 to 25. Specific examples of the aryl group may comprise a phenyl group, a biphenyl group, a triphenyl group, a naphthyl group, an anthryl group, a chrysenyl group, a phenanthrenyl group, a perylenyl group, a fluoranthenyl group, a triphenylenyl group, a phenalenyl group, a pyrenyl group, a tetracenyl group, a pentacenyl group, a fluorenyl group, an indenyl group, an acenaphthylenyl group, a benzofluorenyl group, a spirobifluorenyl group, a 2,3-dihydro-1H-indenyl group, a fused ring thereof, and the like, but are not limited thereto.

(24) In the present specification, the phosphine oxide group is represented by $\text{—P(=O)R}_{101}\text{R}_{102}$, and R₁₀₁ and R₁₀₂ are the same as or different from each other and may be each independently a substituent formed with at least one of hydrogen; deuterium; a halogen group; an alkyl group; an alkenyl group; an alkoxy group; a cycloalkyl group; an aryl group; and a heterocyclic group. Specific examples of the phosphine oxide may comprise a diphenylphosphine oxide group, a dinaphthylphosphine oxide group and the like, but are not limited thereto.

(25) In the present specification, the silyl group is a substituent comprising Si, having the Si atom directly linked as a radical, and is represented by $\text{—SiR}_{\text{sub.104}}\text{R}_{\text{sub.105}}\text{R}_{\text{sub.106}}$. R_{sub.104} to R_{sub.106} are the same as or different from each other, and may be each independently a substituent formed with at least one of hydrogen; deuterium; a halogen group; an alkyl group; an alkenyl group; an alkoxy group; a cycloalkyl group; an aryl group; and a heterocyclic group. Specific examples of the silyl group may comprise a trimethylsilyl group, a triethylsilyl group, a t-butyltrimethylsilyl group, a vinyltrimethylsilyl group, a propyltrimethylsilyl group, a triphenylsilyl

group, a diphenylsilyl group, a phenylsilyl group and the like, but are not limited thereto.

(26) In the present specification, the fluorenyl group may be substituted, and adjacent substituents may bond to each other to form a ring.

(27) When the fluorenyl group is substituted, any one of the following structures may be included, however, the structure is not limited thereto.

(28) ##STR00004##

(29) In the present specification, the heteroaryl group comprises S, O, Se, N or Si as a heteroatom, comprises monocyclic or polycyclic having 2 to 60 carbon atoms, and may be further substituted with other substituents. Herein, the polycyclic means a group in which the heteroaryl group is directly linked to or fused with other cyclic groups. Herein, the other cyclic groups may be a heteroaryl group, but may also be different types of cyclic groups such as a cycloalkyl group, a heterocycloalkyl group and an aryl group. The number of carbon atoms of the heteroaryl group may be from 2 to 60, specifically from 2 to 40 and more specifically from 3 to 25. Specific examples of the heteroaryl group may comprise a pyridyl group, a pyrrolyl group, a pyrimidyl group, a pyridazinyl group, a furanyl group, a thiophene group, an imidazolyl group, a pyrazolyl group, an oxazolyl group, an isoxazolyl group, a triazolyl group, an isothiazolyl group, a triazolyl group, a furazanyl group, an oxadiazolyl group, a thiadiazolyl group, a dithiazolyl group, a tetrazolyl group, a pyranyl group, a thiopyranyl group, a diazinyl group, an oxazinyl group, a triazinyl group, a dioxynyl group, a triazinyl group, a tetrazinyl group, a quinolyl group, an isoquinolyl group, a quinazolinyl group, an isoquinazolinyl group, a quinoxalinyl group, a naphthyridyl group, an acridinyl group, a phenanthridinyl group, an imidazopyridinyl group, a diazanaphthalenyl group, a triazaindene group, an indolyl group, an indolizinyl group, a benzothiazolyl group, a benzoxazolyl group, a benzimidazolyl group, a benzothiophene group, a benzofuran group, a dibenzothiophene group, a dibenzofuran group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenazinyl group, a dibenzosilole group, spirobi(dibenzosilole), a dihydrophenazinyl group, a phenoxazinyl group, a phenanthridyl group, an imidazopyridinyl group, a thienyl group, an indolo[2,3-a]carbazolyl group, an indolo[2,3-b]carbazolyl group, an indolinyl group, a 10,11-dihydro-dibenzo[b,f]azepine group, a 9,10-dihydroacridinyl group, a phenanthrazinyl group, a phenothiazazinyl group, a phthalazinyl group, a naphthylidinyl group, a phenanthrolinyl group, a benzo[c][1,2,5]thiadiazolyl group, a 5,10-dihydrobenzo[b,e][1,4]azasilinyl group, a pyrazolo[1,5-c]quinazolinyl group, a pyrido[1,2-b]indazolyl group, a pyrido[1,2-a]imidazo[1,2-e]indolinyl group, a 5,11-dihydroindeno[1,2-b]carbazolyl group and the like, but are not limited thereto.

(30) In the present specification, the amine group may be selected from the group consisting of a monoalkylamine group; a monoarylamine group; a monoheteroarylamine group; —NH.sub.2; a dialkylamine group; a diarylamine group; a diheteroarylamine group; an alkylarylamine group; an alkylheteroarylamine group; and an arylheteroarylamine group, and although not particularly limited thereto, the number of carbon atoms is preferably from 1 to 30. Specific examples of the amine group may comprise a methylamine group, a dimethylamine group, an ethylamine group, a diethylamine group, a phenylamine group, a naphthylamine group, a biphenylamine group, a dibiphenylamine group, an anthracenylamine group, a 9-methyl-anthracenylamine group, a diphenylamine group, a phenylnaphthylamine group, a ditolylamine group, a phenyltolylamine group, a triphenylamine group, a biphenylnaphthylamine group, a phenylbiphenylamine group, a biphenylfluorenylamine group, a phenyltriphenylenylamine group, a biphenyltriphenylenylamine group and the like, but are not limited thereto.

(31) In the present specification, the arylene group means the aryl group having two bonding sites, that is, a divalent group. The descriptions on the aryl group provided above may be applied thereto except for those that are each a divalent group. In addition, the heteroarylene group means the heteroaryl group having two bonding sites, that is, a divalent group. The descriptions on the heteroaryl group provided above may be applied thereto except for those that are each a divalent

group.

(32) In the present specification, an “adjacent” group may mean a substituent substituting an atom directly linked to an atom substituted by the corresponding substituent, a substituent sterically most closely positioned to the corresponding substituent, or another substituent substituting an atom substituted by the corresponding substituent. For example, two substituents substituting ortho positions in a benzene ring, and two substituents substituting the same carbon in an aliphatic ring may be interpreted as groups “adjacent” to each other.

(33) One embodiment of the present application provides a compound represented by Chemical Formula 1.

(34) In one embodiment of the present application, Chemical Formula 1 may be represented by any one of the following Chemical Formula 2 to Chemical Formula 4.

(35) ##STR00005##

(36) In Chemical Formulae 2 to 4,

(37) X1 to X3, R3 to R11, L1, Ar2, Ar4 and m have the same definitions as in Chemical Formula 1.

(38) In one embodiment of the present application, R1 and R2 are the same as or different from each other, and each independently a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group, or groups adjacent to each other may bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring.

(39) In another embodiment, R1 and R2 are the same as or different from each other, and each independently a C1 to C60 alkyl group; or a C6 to C60 aryl group, or groups adjacent to each other may bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring.

(40) In another embodiment, R1 and R2 are the same as or different from each other, and each independently a C1 to C30 alkyl group; or a C6 to C40 aryl group, or groups adjacent to each other may bond to each other to form a substituted or unsubstituted C6 to C40 aromatic hydrocarbon ring.

(41) In another embodiment, R1 and R2 are the same as or different from each other, and each independently a linear C1 to C10 alkyl group; or a C6 to C20 monocyclic aryl group, or groups adjacent to each other may bond to each other to form a polycyclic C6 to C40 aromatic hydrocarbon ring.

(42) In another embodiment, R1 and R2 are the same as or different from each other, and each independently a methyl group; or a phenyl group, or groups adjacent to each other may bond to each other to form a fluorenyl ring.

(43) In one embodiment of the present application, R3 to R11 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; deuterium; a halogen group; —CN; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R''; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group, or two or more groups adjacent to each other bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring, and

(44) R, R' and R'' are the same as or different from each other, and may be each independently hydrogen; a substituted or unsubstituted C1 to C40 alkyl group; or a substituted or unsubstituted C6 to C40 aryl group.

(45) In another embodiment, R3 to R11 are the same as or different from each other, and may be each independently selected from the group consisting of hydrogen; a halogen group; —CN; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl

group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R'' ; —P(=O)RR' ; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group.

(46) In another embodiment, R3 to R11 are the same as or different from each other, and may be each independently hydrogen; a halogen group; —CN ; a substituted or unsubstituted

(47) C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.

(48) In another embodiment, R3 to R11 are the same as or different from each other, and may be each independently hydrogen; a halogen group; —CN ; a substituted or unsubstituted C6 to C30 aryl group; or a substituted or unsubstituted C2 to C30 heteroaryl group.

(49) In another embodiment, R3 to R11 are the same as or different from each other, and may be each independently hydrogen; a fluoro group (—F); or —CN .

(50) In one embodiment of the present application, L1 may be a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group.

(51) In another embodiment, L1 may be a direct bond; or a substituted or unsubstituted C6 to C60 arylene group.

(52) In another embodiment, L1 may be a direct bond; or a substituted or unsubstituted C6 to C40 arylene group. In another embodiment, L1 may be a direct bond; or a substituted or unsubstituted C6 to C30 arylene group.

(53) In another embodiment, L1 may be a direct bond; or a substituted or unsubstituted monocyclic or polycyclic C6 to C30 arylene group.

(54) In another embodiment, L1 may be a direct bond; or a monocyclic or polycyclic C6 to C30 arylene group unsubstituted or substituted with one or more substituents selected from the group consisting of a C1 to C10 alkyl group, a C6 to C20 aryl group, a C2 to C20 heteroaryl group, —P(=O)RR' and —CN , or a combination of the substituents.

(55) In another embodiment, L1 may be a direct bond; a phenylene group; a biphenylene group; a naphthalene group; a biphenyl group substituted with one or more substituents selected from the group consisting of —P(=O)RR' and —CN ; a phenylene group substituted with a pyridine group unsubstituted or substituted with a methyl group, —CN , a carbazole group, a dibenzofuran group and a naphthyl group unsubstituted or substituted with —CN .

(56) In another embodiment, L1 may be any one of the following structural formulae.

(57) ##STR00006##

(58) In the structural formulae,  custom character means a position linked to the substituents of Chemical Formula 1,

(59) R12 is a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —CN ; or —P(=O)RR' , and

(60) R and R' have the same definitions as in Chemical Formula 1.

(61) In one embodiment of the present application, R12 may be a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —CN ; or —P(=O)RR' .

(62) In another embodiment, R11 may be a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; or —CN .

(63) In another embodiment, R12 may be a substituted or unsubstituted C6 to C40 aryl group; a substituted or unsubstituted C2 to C40 heteroaryl group; or —CN .

(64) In another embodiment, R12 may be a substituted or unsubstituted C6 to C30 aryl group; a substituted or unsubstituted C2 to C30 heteroaryl group; or —CN .

(65) In another embodiment, R12 may be a C6 to C30 aryl group unsubstituted or substituted with —CN or —P(=O)RR' ; a C2 to C30 heteroaryl group unsubstituted or substituted with a C1 to C10

alkyl group; or —CN.

(66) In another embodiment, R12 may be a phenyl group unsubstituted or substituted with —CN or —P(=O)RR'; a dibenzofuran group; a carbazole group; a naphthyl group unsubstituted or substituted with —CN; a pyridine group unsubstituted or substituted with a methyl group; or —CN.

(67) In one embodiment of the present application, X1 to X3 are the same as or different from each other, and each independently N; or CRa, and at least one thereof may be N.

(68) In one embodiment of the present application, X1 is N, X2 is CAr3, and X3 is CAr5, and

(69) Ar3 and Ar5 have the same definition as Ra of Chemical Formula 1.

(70) In one embodiment of the present application, X1 is N, X2 is N, and X3 is CAr5, and Ar5 has the same definition as Ra of Chemical Formula 1.

(71) In one embodiment of the present application, X1 is N, X3 is N, and X2 is CAr3, and

(72) Ar3 has the same definition as Ra of Chemical Formula 1.

(73) In one embodiment of the present application, X1 to X3 are N.

(74) In one embodiment of the present application, X2 is N, X1 is CAr1, and X3 is CAr5, and

(75) Ar1 and Ar5 have the same definition as Ra of Chemical Formula 1.

(76) In one embodiment of the present application, Ra, Ar2 and

(77) Ar4 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R"; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group, or two or more groups adjacent to each other may bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring.

(78) In another embodiment, Ra, Ar2 and Ar4 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C6 to C60 aryl group; and a substituted or unsubstituted C2 to C60 heteroaryl group, or two or more groups adjacent to each other may bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring.

(79) In another embodiment, Ra, Ar2 and Ar4 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C6 to C40 aryl group; and a substituted or unsubstituted C2 to C40 heteroaryl group, or two or more groups adjacent to each other may bond to each other to form a substituted or unsubstituted C2 to C40 heteroring.

(80) In another embodiment, Ra, Ar2 and Ar4 are the same as or different from each other, and each independently hydrogen; or a C6 to C40 aryl group unsubstituted or substituted with one or more substituents selected from the group consisting of a C6 to C40 aryl group and a C2 to C40 heteroaryl group, or two or more groups adjacent to each other may bond to each other to form a C2 to C40 heteroring unsubstituted or substituted with a C6 to C40 aryl group.

(81) In another embodiment, Ra, Ar2 and Ar4 are the same as or different from each other, and each independently hydrogen; a phenyl group unsubstituted or substituted with one or more substituents selected from the group consisting of a phenyl group and a carbazole group; a biphenyl group; or a terphenyl group, or two or more groups adjacent to each other may bond to each other to form a quinoline ring unsubstituted or substituted with a phenyl group.

(82) In one embodiment of the present application,

(83) ##STR00007##

of Chemical Formula 1 may be represented by any one of the following Chemical Formulae 1-1 to 1-5.

(84) ##STR00008##

custom character means a position linked to L1 of Chemical Formula 1,

(85) Ar11 to Ar15 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R''; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group, and

(86) R, R' and R'' have the same definitions as in Chemical Formula 1.

(87) In one embodiment of the present application,

(88) ##STR00009##

of Chemical Formula 1 may be represented by the following Chemical Formula 1-6 or 1-7.

(89) ##STR00010##

(90) In Chemical Formulae 1-6 and 1-7,

(91) ##STR00011##

means a position linked to L1 of Chemical Formula 1, and

(92) R21 is hydrogen; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.

(93) In one embodiment of the present application, Ar11 and Ar15 are the same as or different from each other, and may be each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R''; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group.

(94) In another embodiment, Ar11 and Ar15 are the same as or different from each other, and may be each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C6 to C40 aryl group; and a substituted or unsubstituted C2 to C40 heteroaryl group.

(95) In another embodiment, Ar11 and Ar15 are the same as or different from each other, and may be each independently hydrogen; or a C6 to C40 aryl group unsubstituted or substituted with one or more substituents selected from the group consisting of a C6 to C40 aryl group and a C2 to C40 heteroaryl group.

(96) In another embodiment, Ar11 and Ar15 are the same as or different from each other, and may be each independently hydrogen; a phenyl group unsubstituted or substituted with one or more substituents selected from the group consisting of a phenyl group and a carbazole group; a biphenyl group; or a terphenyl group.

(97) In one embodiment of the present application, R21 is hydrogen; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.

(98) In another embodiment, R21 is hydrogen; or a substituted or unsubstituted C6 to C60 aryl group.

(99) In another embodiment, R21 is hydrogen; or a substituted or unsubstituted C6 to C40 aryl group.

(100) In another embodiment, R21 is hydrogen; or monocyclic or polycyclic C6 to C40 aryl group.

(101) In another embodiment, R21 is hydrogen; or a monocyclic C6 to C20 aryl group.

(102) In another embodiment, R21 is hydrogen; or a phenyl group.

(103) In one embodiment of the present application, Ar12 is represented by

(104) ##STR00012##

and Ar14 is a substituted or unsubstituted C6 to C60 aryl group,

(105) L2 is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group,

(106) Z2 is a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2

to C60 heteroaryl group, and
(107) a and b are the same as or different from each other and each an integer of 1 to 6, and when a and b are 2 or greater, substituents in the parentheses are the same as or different from each other.
(108) In one embodiment of the present application, Ar12 has the same definition as Ar2 of Chemical Formula 1, and Ar14 has the same definition as Ar4 of Chemical Formula 1.
(109) In one embodiment of the present application, Ar12 is represented by
(110) ##STR00013##
and Ar14 is a substituted or unsubstituted C6 to C60 aryl group,
(111) L2 is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group,
(112) Z2 is a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group, and
(113) a and b are the same as or different from each other and each an integer of 1 to 6, and when a and b are 2 or greater, substituents in the parentheses are the same as or different from each other.
(114) In one embodiment of the present application, Ar12 has the same definition as Ar2 of Chemical Formula 1, and Ar14 has the same definition as Ar4 of Chemical Formula 1.
(115) In one embodiment of the present application, Ar12 is represented by
(116) ##STR00014##
and Ar14 may be a substituted or unsubstituted C6 to C60 aryl group.
(117) In another embodiment, Ar12 is represented by
(118) ##STR00015##
and Ar14 may be a substituted or unsubstituted C6 to C40 aryl group.
(119) In another embodiment, Ar12 is represented by
(120) ##STR00016##
and Ar14 may be a C6 to C40 aryl group.
(121) In another embodiment, Ar12 is represented by
(122) ##STR00017##
and Ar14 may be a C6 to C20 aryl group.
(123) In another embodiment, Ar12 is represented by
(124) ##STR00018##
and Ar14 may be a monocyclic or polycyclic C6 to C20 aryl group.
(125) In another embodiment, Ar12 is represented by
(126) ##STR00019##
and Ar14 may be a phenyl group or a biphenyl group.
(127) In one embodiment of the present application, L2 may be a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group.
(128) In another embodiment, L2 may be a direct bond; or a substituted or unsubstituted C6 to C60 arylene group.
(129) In another embodiment, L2 may be a direct bond; or a substituted or unsubstituted C6 to C40 arylene group.
(130) In another embodiment, L2 may be a direct bond; or a C6 to C40 arylene group.
(131) In another embodiment, L2 may be a direct bond; or a monocyclic or polycyclic C6 to C20 arylene group.
(132) In another embodiment, L2 may be a direct bond; a phenylene group; or a biphenylene group.
(133) In one embodiment of the present application, Z2 may be a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.
(134) In another embodiment, Z2 may be a substituted or unsubstituted C6 to C40 aryl group; or a substituted or unsubstituted C2 to C40 heteroaryl group.
(135) In another embodiment, Z2 may be a C6 to C40 aryl group; or a C2 to C40 heteroaryl group.

(136) In another embodiment, Z2 may be a C6 to C20 aryl group; or a C2 to C20 heteroaryl group.
(137) In another embodiment, Z2 may be a C6 to C20 aryl group; or a C2 to C20 heteroaryl group comprising N.

(138) In another embodiment, Z2 may be a phenyl group; a biphenyl group; or a carbazole group.

(139) In one embodiment of the present application, R, R' and R'' are the same as or different from each other, and may be each independently hydrogen; a substituted or unsubstituted C1 to C40 alkyl group; or a substituted or unsubstituted C6 to C40 aryl group.

(140) In another embodiment, R, R' and R'' are the same as or different from each other, and may be each independently a substituted or unsubstituted C1 to C20 alkyl group; or a substituted or unsubstituted C6 to C20 aryl group.

(141) In another embodiment, R, R' and R'' are the same as or different from each other, and may be each independently a C1 to C20 alkyl group; or a C6 to C20 aryl group.

(142) In another embodiment, R, R' and R'' are the same as or different from each other, and may be each independently a C1 to C20 linear alkyl group; or a C6 to C20 monocyclic aryl group.

(143) In another embodiment, R, R' and R'' may be a methyl group; or a phenyl group.

(144) In another embodiment, R, R' and R'' may be a methyl group.

(145) In the heterocyclic compound provided in one embodiment of the present application, Chemical Formula 1 is represented by any one of the following compounds.

(146) ##STR00020## ##STR00021## ##STR00022## ##STR00023## ##STR00024##
##STR00025## ##STR00026## ##STR00027## ##STR00028## ##STR00029## ##STR00030##
##STR00031## ##STR00032## ##STR00033## ##STR00034## ##STR00035## ##STR00036##
##STR00037## ##STR00038## ##STR00039## ##STR00040## ##STR00041## ##STR00042##
##STR00043## ##STR00044## ##STR00045## ##STR00046## ##STR00047## ##STR00048##
##STR00049## ##STR00050## ##STR00051## ##STR00052## ##STR00053## ##STR00054##
##STR00055## ##STR00056## ##STR00057## ##STR00058## ##STR00059## ##STR00060##
##STR00061## ##STR00062## ##STR00063## ##STR00064## ##STR00065## ##STR00066##
##STR00067## ##STR00068## ##STR00069## ##STR00070##

(147) ##STR00071## ##STR00072## ##STR00073## ##STR00074## ##STR00075##
##STR00076## ##STR00077## ##STR00078## ##STR00079## ##STR00080## ##STR00081##
##STR00082## ##STR00083## ##STR00084## ##STR00085## ##STR00086## ##STR00087##
##STR00088## ##STR00089## ##STR00090## ##STR00091## ##STR00092## ##STR00093##
##STR00094## ##STR00095## ##STR00096## ##STR00097## ##STR00098## ##STR00099##
##STR00100## ##STR00101## ##STR00102## ##STR00103## ##STR00104## ##STR00105##
##STR00106## ##STR00107## ##STR00108## ##STR00109## ##STR00110## ##STR00111##
##STR00112## ##STR00113## ##STR00114## ##STR00115## ##STR00116## ##STR00117##
##STR00118## ##STR00119## ##STR00120## ##STR00121## ##STR00122## ##STR00123##
##STR00124## ##STR00125## ##STR00126## ##STR00127## ##STR00128## ##STR00129##
##STR00130## ##STR00131## ##STR00132## ##STR00133##

(148) In addition, by introducing various substituents to the structure of Chemical Formula 1, compounds having unique properties of the introduced substituents may be synthesized. For example, by introducing substituents normally used as hole injection layer materials, hole transfer layer materials, light emitting layer materials, electron transfer layer materials and charge generation layer materials used for manufacturing an organic light emitting device to the core structure, materials satisfying conditions required for each organic material layer may be synthesized.

(149) In addition, by introducing various substituents to the structure of Chemical Formula 1, the energy band gap may be finely controlled, and meanwhile, properties at interfaces between organic materials are enhanced, and material applications may become diverse.

(150) Meanwhile, the compound has a high glass transition temperature (Tg) and thereby has superior thermal stability. Such an increase in the thermal stability becomes an important factor in

providing driving stability to a device.

(151) In addition, one embodiment of the present application provides an organic light emitting device comprising a first electrode; a second electrode provided opposite to the first electrode; and one or more organic material layers provided between the first electrode and the second electrode, wherein one or more layers of the organic material layers comprise the heterocyclic compound represented by Chemical Formula 1.

(152) In one embodiment of the present application, the first electrode may be an anode, and the second electrode may be a cathode.

(153) In another embodiment, the first electrode may be a cathode, and the second electrode may be an anode.

(154) Specific descriptions on the heterocyclic compound represented by Chemical Formula 1 are the same as the descriptions provided above.

(155) In one embodiment of the present application, the organic light emitting device may be a blue organic light emitting device, and the heterocyclic compound according to Chemical Formula 1 may be used as a material of the blue organic light emitting device.

(156) In one embodiment of the present application, the organic light emitting device may be a green organic light emitting device, and the heterocyclic compound according to Chemical Formula 1 may be used as a material of the green organic light emitting device.

(157) In one embodiment of the present application, the organic light emitting device may be a red organic light emitting device, and the heterocyclic compound according to Chemical Formula 1 may be used as a material of the red organic light emitting device.

(158) The organic light emitting device of the present disclosure may be manufactured using common organic light emitting device manufacturing methods and materials except that one or more of the organic material layers are formed using the heterocyclic compound described above.

(159) The heterocyclic compound may be formed into an organic material layer through a solution coating method as well as a vacuum deposition method when manufacturing the organic light emitting device. Herein, the solution coating method means spin coating, dip coating, inkjet printing, screen printing, a spray method, roll coating and the like, but is not limited thereto.

(160) The organic material layer of the organic light emitting device of the present disclosure may be formed in a single layer structure, but may be formed in a multilayer structure in which two or more organic material layers are laminated. For example, the organic light emitting device of the present disclosure may have a structure comprising a hole injection layer, a hole transfer layer, a light emitting layer, an electron transfer layer, an electron injection layer and the like as the organic material layer. However, the structure of the organic light emitting device is not limited thereto, and may comprise a smaller number of organic material layers.

(161) In the organic light emitting device of the present disclosure, the organic material layer comprises an electron injection layer or a hole transfer layer, and the electron injection layer or the hole transfer layer may comprise the heterocyclic compound.

(162) In the organic light emitting device of the present disclosure, the organic material layer comprises an electron transfer layer, and the electron transfer layer may comprise the heterocyclic compound.

(163) In another organic light emitting device, the organic material layer comprises an electron blocking layer or a hole blocking layer, and the electron blocking layer or the hole blocking layer may comprise the heterocyclic compound.

(164) In another organic light emitting device, the organic material layer comprises a hole blocking layer, and the hole blocking layer may comprise the heterocyclic compound.

(165) In another organic light emitting device, the organic material layer comprises an electron blocking layer, and the electron blocking layer may comprise the heterocyclic compound.

(166) In one embodiment of the present application, the organic material layer comprises a hole injection layer, and the hole injection layer may comprise the heterocyclic compound.

(167) In one embodiment of the present application, the organic material layer comprises a hole transfer layer, and the hole transfer layer may comprise the heterocyclic compound.

(168) In another organic light emitting device, the organic material layer comprises an electron transfer layer, a light emitting layer or a hole blocking layer, and the electron transfer layer, the light emitting layer or the hole blocking layer may comprise the heterocyclic compound.

(169) The organic light emitting device of the present disclosure may further comprise one, two or more layers selected from the group consisting of a light emitting layer, a hole injection layer, a hole transfer layer, an electron injection layer, an electron transfer layer, an electron blocking layer and a hole blocking layer.

(170) FIG. 1 to FIG. 4 illustrate a lamination order of electrodes and organic material layers of an organic light emitting device according to one embodiment of the present application. However, the scope of the present application is not limited to these diagrams, and structures of organic light emitting devices known in the art may also be used in the present application.

(171) FIG. 1 illustrates an organic light emitting device in which an anode (200), an organic material layer (300) and a cathode (400) are consecutively laminated on a substrate (100).

However, the structure is not limited to such a structure, and as illustrated in FIG. 2, an organic light emitting device in which a cathode, an organic material layer and an anode are consecutively laminated on a substrate may also be obtained.

(172) FIG. 3 illustrates a case of the organic material layer being a multilayer. The organic light emitting device according to FIG. 3 comprises a hole injection layer (301), a hole transfer layer (302), a light emitting layer (303), a hole blocking layer (304), an electron transfer layer (305) and an electron injection layer (306). However, the scope of the present application is not limited to such a lamination structure, and as necessary, layers other than the light emitting layer may not be included, and other necessary functional layers may be further added.

(173) The organic material layer comprising Chemical Formula 1 may further comprise other materials as necessary.

(174) In addition, the organic light emitting device according to one embodiment of the present application comprises an anode, a cathode, and two or more stacks provided between the anode and the cathode, the two or more stacks each independently comprise a light emitting layer, a charge generation layer is included between the two or more stacks, and the charge generation layer comprises the compound represented by Chemical Formula 1.

(175) In addition, the organic light emitting device according to one embodiment of the present application comprises an anode, a first stack provided on the anode and comprising a first light emitting layer, a charge generation layer provided on the first stack, a second stack provided on the charge generation layer and comprising a second light emitting layer, and a cathode provided on the second stack. Herein, the charge generation layer may comprise the heterocyclic compound represented by Chemical Formula 1. In addition, the first stack and the second stack may each independently further comprise one or more types of the hole injection layer, the hole transfer layer, the hole blocking layer, the electron transfer layer, the electron injection layer and the like described above.

(176) As the organic light emitting device according to one embodiment of the present application, an organic light emitting device having a 2-stack tandem structure is schematically illustrated in FIG. 4.

(177) Herein, the first electron blocking layer, the first hole blocking layer, the second hole blocking layer and the like described in FIG. 4 may not be included in some cases.

(178) In the organic light emitting device according to one embodiment of the present application, materials other than the compound of Chemical Formula 1 are illustrated below, however, these are for illustrative purposes only and not for limiting the scope of the present application, and may be replaced by materials known in the art.

(179) As the anode material, materials having relatively large work function may be used, and

transparent conductive oxides, metals, conductive polymers or the like may be used. Specific examples of the anode material comprise metals such as vanadium, chromium, copper, zinc and gold, or alloys thereof; metal oxides such as zinc oxide, indium oxide, indium tin oxide (ITO) and indium zinc oxide (IZO); combinations of metals and oxides such as ZnO:Al or SnO₂:Sb; conductive polymers such as poly(3-methylthiophene), poly[3,4-(ethylene-1,2-dioxy)thiophene] (PEDOT), polypyrrole and polyaniline, and the like, but are not limited thereto.

(180) As the cathode material, materials having relatively small work function may be used, and metals, metal oxides, conductive polymers or the like may be used. Specific examples of the cathode material comprise metals such as magnesium, calcium, sodium, potassium, titanium, indium, yttrium, lithium, gadolinium, aluminum, silver, tin and lead, or alloys thereof; multilayer structure materials such as LiF/Al or LiO₂/Al, and the like, but are not limited thereto.

(181) As the hole injection material, known hole injection materials may be used, and for example, phthalocyanine compounds such as copper phthalocyanine disclosed in U.S. Pat. No. 4,356,429, or starburst-type amine derivatives such as tris(4-carbazoyl-9-ylphenyl)amine (TCTA), 4,4',4''-tri[phenyl(m-tolyl)amino]triphenylamine (m-MTDATA) or 1,3,5-tris[4-(3-methylphenylphenylamino)phenyl]benzene (m-MTDAPB) described in the literature [Advanced Material, 6, p. 677 (1994)], polyaniline/dodecylbenzene sulfonic acid, poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate), polyaniline/camphor sulfonic acid or polyaniline/poly(4-styrene-sulfonate) that are conductive polymers having solubility, and the like, may be used.

(182) As the hole transfer material, pyrazoline derivatives, arylamine-based derivatives, stilbene derivatives, triphenyldiamine derivatives and the like may be used, and low molecular or high molecular materials may also be used.

(183) As the electron transfer material, metal complexes of oxadiazole derivatives, anthraquinodimethane and derivatives thereof, benzoquinone and derivatives thereof, naphthoquinone and derivatives thereof, anthraquinone and derivatives thereof, tetracyanoanthraquinodimethane and derivatives thereof, fluorenone derivatives, diphenyldicyanoethylene and derivatives thereof, diphenoquinone derivatives, 8-hydroxyquinoline and derivatives thereof, and the like, may be used, and high molecular materials may also be used as well as low molecular materials.

(184) As examples of the electron injection material, LiF is typically used in the art, however, the present application is not limited thereto.

(185) As the light emitting material, red, green or blue light emitting materials may be used, and as necessary, two or more light emitting materials may be mixed and used. Herein, two or more light emitting materials may be used by being deposited as individual sources of supply or by being premixed and deposited as one source of supply. In addition, fluorescent materials may also be used as the light emitting material, however, phosphorescent materials may also be used. As the light emitting material, materials emitting light by bonding electrons and holes injected from an anode and a cathode, respectively, may be used alone, however, materials having a host material and a dopant material involving in light emission together may also be used.

(186) When mixing light emitting material hosts, same series hosts may be mixed, or different series hosts may be mixed. For example, any two or more types of materials among n-type host materials or p-type host materials may be selected and used as a host material of a light emitting layer.

(187) The organic light emitting device according to one embodiment of the present application may be a top-emission type, a bottom-emission type or a dual-emission type depending on the materials used.

(188) The heterocyclic compound according to one embodiment of the present application may also be used in an organic electronic device comprising an organic solar cell, an organic photo conductor, an organic transistor and the like under a similar principle used in the organic light

emitting device.

(189) Hereinafter, the present specification will be described in more detail with reference to examples, however, these are for illustrative purposes only, and the scope of the present application is not limited thereto.

PREPARATION EXAMPLE

[Preparation Example 1] Preparation of Compound 5

(190) ##STR00134##

Preparation of Compound 5-2










(191) 1,4-Dioxane (100 ml) was introduced to 6-bromo-11,11-dimethyl-11H-benzo[a]fluorene (A) (10 g, 0.03 mol, 1 eq.), bis(pinacolato)diboron (11.8 g, 0.046 mol, 1.5 eq.), KOAc (9.1 g, 0.09 mol, 3 eq.) and Pd(dppf)Cl.sub.2 (2.2 g, 0.003 mol, 0.1 eq.), and the result was stirred for 6 hours at 100° C. After terminating the reaction by introducing water thereto, the result was extracted using methylene chloride (MC) and water. Then, moisture was removed therefrom using MgSO.sub.4. The result was separated using a silica gel column to obtain Compound 5-2 (9 g) in a 78% yield.

(192) Preparation of Compound 5

(193) 1,4-Dioxane (100 ml) was introduced to 2-(4-bromophenyl)-4,6-diphenyl-1,3,5-triazine (B) (10 g, 0.025 mol, 1 eq.), Compound 5-2 (10 g, 0.027 mol, 1.05 eq.), K.sub.3PO.sub.4 (11 g, 0.05 mol, eq.) and Pd(PPh.sub.3).sub.4 (1.5 g, 0.001 mol, 0.05 eq.), and the result was stirred for 6 hours at 100° C. After terminating the reaction by introducing water thereto, the result was extracted using methylene chloride (MC) and water. Then, moisture was removed therefrom using MgSO.sub.4. The result was separated using a silica gel column to obtain Compound 5 (7 g) in a 49% yield.

(194) Target compounds were synthesized in the same manner as in Preparation Example 1 except that Intermediate A of the following Table 1 was used instead of 6-bromo-11,11-dimethyl-11H-benzo[a]fluorene (A), and Intermediate B of the following Table 1 was used instead of 2-(4-bromophenyl)-4,6-diphenyl-1,3,5-triazine (B).

(195) TABLE-US-00001 TABLE 1 Compound No. Intermediate A Intermediate B Yield

		63% 9			67% 10
		59% 17			51% 18
		62% 21			60% 22
		60% 25			55% 27
		61% 29			58% 30
		53% 54			66% 117
		60% 118			52% 145
		63% 146			61% 225
		61% 227			70% 337
		67% 338			60%

(196) Compounds 1 to 416 other than the compounds described in Preparation Example 1 and Table 1 were also prepared in the same manner as above, and the synthesis identification results are shown in Table 2 and Table 3. Table 2 shows measurement values of ¹H NMR (CDCl.sub.3, 200 Mz), and Table 3 shows measurement values of FD-mass spectrometry (FD-MS: field desorption mass spectrometry).

(197) TABLE-US-00002 TABLE 2 Compound ¹H NMR (CDCl.sub.3, 200 Mz) 5 δ = 8.28(4 H, m), 8.18(1 H, d), 8.09(2 H, m), 7.85(3 H, m), 7.54~7.41(10 H, m), 7.25(3 H, m), 1.85(6 H, s) 9 δ = 8.28(6 H, m), 8.05(2 H, m), 7.79(1 H, s), 7.70(1 H, s), 7.57~7.41(10 H, m), 7.24(3 H, m), 1.85(6 H, s) 10 δ = 8.28(2 H, m), 8.23(1 H, s), 8.18(1 H, d), 8.05(2 H, m), 7.79(5 H, m), 7.57~7.41(12 H, m), 7.24(1 H, t), 1.85(6 H, s) 17 δ = 8.28(6 H, m), 8.05(2 H, m), 7.79(1 H, s), 7.70(1 H, s), 7.61~7.41(12 H, m), 7.25(5 H, m), 1.85(6 H, s) 18 δ = 8.28(2 H, m), 8.23(1 H, s), 8.18(1 H, d), 8.05(2 H, m), 7.79(5 H, m), 7.61~7.41(12 H, m), 7.25(5 H, m), 1.85(6 H, s) 21 δ = 8.28(4 H, m), 8.18(1 H, d), 8.09(2 H, m), 7.85(2 H, m), 7.79(1 H, s), 7.70(1 H, s), 7.61~7.41(13 H, m), 7.25(3 H,

m), 1.85(6 H, s) 22 δ = 8.30(2 H, t), 8.28(2 H, m), 8.23(1 H, s), 8.18(1 H, d), 8.05(2 H, m), 7.79 (5 H, m), 7.70(1 H, s), 7.61~7.41 (13 H, m) , 7.25(1 H, t), 1.85(6 H, s) 25 δ = 8.28(6 H, m), 8.09 (2 H, m), 7.79 (1 H, s), 7.70(2 H, s), 7.61~7.41(15 H, m), 7.24(1 H, t), 1.85(6 H, s) 27 δ = 8.23(3 H, m), 8.05(2 H, m), 7.79(5 H, m), 7.70(2 H, s), 7.61~7.41(15 H, m), 7.25(1 H, t), 1.85(6 H, s) 29 δ = 8.28(2 H, m), 8.18(1 H, d), 8.09(2 H, m), 7.85(2 H, m), 7.79(1 H, s), 7.61~7.41 (12 H, m), 7.25(3 H, m), 1.85(6 H, s) 30 δ = 8.30(6 H, m), 8.05(2 H, m), 7.85(2 H, m), 7.79(1 H, s), 7.61~7.41(12 H, m), 7.25(1 H, t), 1.85(6 H, s) 54 δ = 8.55(1 H, d), 8.12(8 H, m), 7.94(1 H, d), 7.79(2 H, m), 7.61~7.25 (15 H, m), 1.85(6 H, s) 117 δ = 8.28(4 H, m), 8.18(1 H, d), 8.05(2 H, m), 7.85, (2 H, m), 7.92(1 H, s) 7.61~7.2 6 (19 H, m), 7.11(4 H, m) 118 δ = 8.30(6 H, m), 8.09(2 H, m), 7.79(3 H, m), 7.61~7.25(19 H, m), 7.11(4 H, m) 145 δ = 8.24(4 H, m), 8.09(2 H, m), 7.79(1 H, s), 7.70(1 H, s), 7.61~7.41(21 H, m), 7.11(4 H, m) 146 δ = 8.23(4 H, m), 8.09(2 H, m), 8.18(1 H, d), 8.09(2 H, m), 7.61~7.41(21 H, m), 7.11(4 H, m) 225 δ = 8.28(4 H, m), 8.18(1 H, d), 8.09(2 H, m), 7.75(3 H, m), 7.51~7.41(12 H, m), 7.19(5 H, m) 227 δ = 8.23(1 H, s), 8.18(1 H, d), 8.09(2 H, m), 7.79(7 H, m), 7.51~7.41(12 H, m), 7.19(5 H, m) 337 δ = 8.28(4 H, m), 8.18(1 H, d), 8.05(2 H, m), 7.79(1 H, s), 7.76(3 H, m), 7.61(1 H, d), 7.51~7.41(14 H, m), 7.24(1 H, t), 1.85(6 H, s) 338 δ = 8.28(2 H, m), 8.23(1 H, s), 8.18(1 H, d), 8.05(2 H, m), 7.79(3 H, m), 7.76(3 H, m), 7.61(1 H, d) 7.51~7.41(14 H, m), 7.24(1 H, t), 1.85(6 H, s)

(198) TABLE-US-00003 TABLE 3 Compound FD-MS 5 m/z = 551.68 (C₄₀H₂₉N₃ = 551.24) 9 m/z = 551.68 (C₄₀H₂₉N₃ = 551.24) 10 m/z = 550.69 (C₄₁H₃₀N₂ = 550.24) 17 m/z = 627.77 (C₄₆H₃₃N₃ = 627.27) 18 m/z = 626.79 (C₄₆H₃₃N₃ = 626.79) 21 m/z = 627.77 (C₄₆H₃₃N₃ = 627.27) 22 m/z = 626.79 (C₄₆H₃₃N₃ = 626.79) 25 m/z = 627.77 (C₄₆H₃₃N₃ = 627.27) 27 m/z = 626.79 (C₄₆H₃₃N₃ = 626.79) 29 m/z = 551.68 (C₄₀H₂₉N₃ = 551.24) 30 m/z = 550.69 (C₄₁H₃₀N₂ = 550.24) 54 m/z = 639.79 (C₄₇H₃₃N₃ = 639.27) 117 m/z = 675.82 (C₅₀H₃₃N₃ = 675.27) 118 m/z = 674.83 (C₅₁H₃₄N₂ = 674.27) 145 m/z = 675.82 (C₅₀H₃₃N₃ = 675.27) 146 m/z = 674.83 (C₅₁H₃₄N₂ = 674.27) 225 m/z = 597.71 (C₄₄H₂₇N₃O = 597.22) 227 m/z = 596.72 (C₄₅H₂₈N₂ = 596.23) 337 m/z = 627.77 (C₄₆H₃₃N₃ = 627.27) 338 m/z = 626.79 (C₄₆H₃₃N₃ = 626.79)

EXPERIMENTAL EXAMPLE

Experimental Example 1

(199) 1) Manufacture of Organic Light Emitting Device

(200) A transparent indium tin oxide (ITO) electrode thin film obtained from glass for an OLED (manufactured by Samsung-Corning Co., Ltd.) was ultrasonic cleaned using trichloroethylene, acetone, ethanol and distilled water consecutively for 5 minutes each, stored in isopropanol, and used. Next, the ITO substrate was installed in a substrate folder of a vacuum deposition apparatus, and the following 4,4',4''-tris(N,N-(2-naphthyl)-phenylamino)triphenylamine (2-TNATA) was introduced to a cell in the vacuum deposition apparatus.

(201) ##STR00175##

(202) Subsequently, the chamber was evacuated until the degree of vacuum therein reached 10.sup.-6 torr, and then 2-TNATA was evaporated by applying a current to the cell to deposit a hole injection layer having a thickness of 600 Å on the ITO substrate. To another cell in the vacuum deposition apparatus, the following N,N'-bis(α -naphthyl)-N,N'-diphenyl-4,4'-diamine (NPB) was introduced, and evaporated by applying a current to the cell to deposit a hole transfer layer having a thickness of 300 Å on the hole injection layer.

(203) ##STR00176##

(204) After forming the hole injection layer and the hole transfer layer as above, a blue light emitting material having a structure as below was deposited thereon as a light emitting layer. Specifically, in one side cell in the vacuum deposition apparatus, H1, a blue light emitting host material, was vacuum deposited to a thickness of 200 Å, and D1, a blue light emitting dopant material, was vacuum deposited thereon by 5% with respect to the host material.

(205) ##STR00177##

(206) Subsequently, a compound of the following Structural Formula E1 was deposited to a thickness of 300 Å as an electron transfer layer.

(207) ##STR00178##

(208) As an electron injection layer, lithium fluoride (LiF) was deposited to a thickness of 10 Å, and an Al cathode was employed to a thickness of 1,000 Å, and as a result, an OLED was manufactured. Meanwhile, all the organic compounds required to manufacture the OLED were vacuum sublimation purified under 10.sup.-8 torr to 10.sup.-6 torr by each material to be used in the OLED manufacture.

(209) Organic electroluminescent devices were manufactured in the same manner as in Experimental Example 1 except that compounds shown in the following Table 4 were used instead of E1 used when forming the electron transfer layer. Results of measuring driving voltage, light emission efficiency, color coordinate (CIE) and lifetime of the blue organic light emitting devices manufactured according to the present disclosure are as shown in Table 4.

(210) TABLE-US-00004 TABLE 4 Light Driving Emission Life- Com- Voltage Efficiency CIE
time pound (V) (cd/A) (x, y) (T95)
Example 1 5 4.90 6.67 (0.134, 0.101) 43
Example 2 9 4.98 6.71 (0.134, 0.102) 40
Example 3 10 4.80 6.72 (0.134, 0.101) 41
Example 4 17 4.94 6.78 (0.134, 0.100) 41
Example 5 18 4.81 6.77 (0.134, 0.100) 48
Example 6 21 4.86 6.70 (0.134, 0.101) 48
Example 7 22 4.90 6.83 (0.134, 0.100) 47
Example 8 25 4.92 6.74 (0.134, 0.101) 40
Example 9 27 4.88 6.72 (0.134, 0.102) 46
Example 10 29 5.02 6.80 (0.134, 0.100) 43
Example 11 30 4.99 6.72 (0.134, 0.100) 49
Example 12 54 5.00 6.84 (0.134, 0.100) 42
Example 13 117 4.98 6.73 (0.134, 0.101) 50
Example 14 118 4.89 6.83 (0.134, 0.102) 45
Example 15 145 4.92 6.80 (0.134, 0.101) 43
Example 16 146 4.90 6.70 (0.134, 0.100) 51
Example 17 225 4.96 6.83 (0.134, 0.100) 46
Example 18 227 4.98 6.85 (0.134, 0.100) 48
Example 19 337 5.09 6.80 (0.134, 0.101) 52
Example 20 338 4.98 6.88 (0.134, 0.101) 50
Comparative E1 5.60 6.10 (0.134, 0.101) 30
Example 1 Comparative E2 5.50 6.13 (0.134, 0.101) 32
Example 2 Comparative E3 5.53 6.22 (0.134, 0.100) 31
Example 3 Comparative E4 5.57 6.27 (0.134, 0.100) 32
Example 4 Comparative E5 5.61 6.19 (0.134, 0.101) 30
Example 5 Comparative E6 5.52 6.20 (0.134, 0.101) 33
Example 6 Comparative E7 5.50 6.16 (0.134, 0.100) 33
Example 7 Comparative E8 5.98 5.92 (0.134, 0.101) 35
Example 8

(211) ##STR00179## ##STR00180## ##STR00181##

(212) As seen from the results of Table 4, the organic light emitting device using the electron transfer layer material of the blue organic light emitting device of the present disclosure had lower driving voltage and significantly improved light emission efficiency and lifetime compared to Comparative Examples 1 to 8. Such a result is considered to be due to the fact that, when using the compound having proper length and strength, and flatness as an electron transfer layer, a compound in an excited state is made by receiving electrons under a specific condition, and particularly when an excited state is formed in the hetero-skeleton site of the compound, excited energy will move to a stable state before the excited hetero-skeleton site goes through other reactions, and as a result, the relatively stabilized compound is capable of efficiently transferring electrons without the compound being decomposed or destroyed. For reference, those that are stable when excited are considered to be aryl or acene-based compounds or polycyclic hetero-compounds. Accordingly, it is considered that excellent results in all aspects of driving, efficiency and lifetime were obtained by the compound of the present disclosure enhancing enhanced electron-transfer properties or improved stability.

(213) The compounds of Examples 1 to 20 have an azine-based substituent having excellent electron transfer properties at a specific position on the skeleton having a fluorene group, and it was identified that, through adjusting band gap and T1 value by strengthening electron withdrawing properties, superior efficiency and driving were obtained when comprising the compounds in the organic light emitting device.

(214) Particularly, when using the azine derivative as the electron transfer layer, it was identified that superior electron withdrawing properties of the azine functional group improved the flow of

electrons enhancing electron transfer capability of the electron transfer layer, and by combining the azine moiety with a substituent with enhanced hole properties, planarity of the azine derivative and the glass transition temperature increased, which increased thermal stability of the compound. It was also identified that electron transfer capability and hole blocking capability were enhanced through adjusting band gap and T1 value, and molecular stability increased as well, and as a result, the device had lowered driving voltage, enhanced light efficiency, and lifetime properties of the device were enhanced due to thermal stability of the compound.

Experimental Example 2

(215) 1) Manufacture of Organic Light Emitting Device

(216) A transparent indium tin oxide (ITO) electrode thin film obtained from glass for an OLED (manufactured by Samsung-Corning Co., Ltd.) was ultrasonic cleaned using trichloroethylene, acetone, ethanol and distilled water consecutively for 5 minutes each, stored in isopropanol, and used. Next, the ITO substrate was installed in a substrate folder of a vacuum deposition apparatus, and the following 4,4',4''-tris(N,N-(2-naphthyl)-phenylamino)triphenylamine (2-TNATA) was introduced to a cell in the vacuum deposition apparatus.

(217) ##STR00182##

(218) Subsequently, the chamber was evacuated until the degree of vacuum therein reached 10.sup.-6 torr, and then 2-TNATA was evaporated by applying a current to the cell to deposit a hole injection layer having a thickness of 600 Å on the ITO substrate. To another cell in the vacuum deposition apparatus, the following N,N'-bis(α-naphthyl)-N,N'-diphenyl-4,4'-diamine (NPB) was introduced, and evaporated by applying a current to the cell to deposit a hole transfer layer having a thickness of 300 Å on the hole injection layer.

(219) ##STR00183##

(220) After forming the hole injection layer and the hole transfer layer as above, a blue light emitting material having a structure as below was deposited thereon as a light emitting layer. Specifically, in one side cell in the vacuum deposition apparatus, H1, a blue light emitting host material, was vacuum deposited to a thickness of 200 Å, and D1, a blue light emitting dopant material, was vacuum deposited thereon by 5% with respect to the host material.

(221) ##STR00184##

(222) Subsequently, a compound of the following Structural Formula E1 was deposited to a thickness of 300 Å as an electron transfer layer.

(223) ##STR00185##

(224) As an electron injection layer, lithium fluoride (LiF) was deposited to a thickness of 10 Å, and an Al cathode was employed to a thickness of 1,000 Å, and as a result, an OLED was manufactured. Meanwhile, all the organic compounds required to manufacture the OLED were vacuum sublimation purified under 10.sup.-6 torr to 10.sup.-8 torr by each material to be used in the OLED manufacture. Organic electroluminescent devices were manufactured in the same manner as in Experimental Example 2 except that, after forming the electron transfer layer E1 to a thickness of 250 Å, a hole blocking layer was formed to a thickness of 50 Å on the electron transfer layer using compounds shown in the following Table 5. Results of measuring driving voltage, light emission efficiency, color coordinate (CIE) and lifetime of the blue organic light emitting devices manufactured according to the present disclosure are as shown in the following Table 5.

(225) TABLE-US-00005 TABLE 5 Light Driving Emission Life- Com- Voltage Efficiency CIE
time pound (V) (cd/A) (x, y) (T95) Example 21 5 5.00 6.51 (0.134, 0.101) 58 Example 22 9 5.00
6.67 (0.134, 0.100) 54 Example 23 10 4.96 6.38 (0.134, 0.100) 57 Example 24 17 4.99 6.55 (0.134,
0.100) 53 Example 25 18 4.80 6.61 (0.134, 0.101) 59 Example 26 21 4.89 6.68 (0.134, 0.100) 60
Example 27 22 4.89 6.51 (0.134, 0.100) 57 Example 28 25 4.81 6.59 (0.134, 0.101) 60 Example 29
27 4.87 6.49 (0.134, 0.101) 60 Example 30 29 4.88 6.44 (0.134, 0.102) 59 Example 31 30 4.87
6.60 (0.134, 0.101) 54 Example 32 54 4.90 6.61 (0.134, 0.100) 53 Example 33 117 5.02 6.54
(0.134, 0.101) 52 Example 34 118 4.93 6.39 (0.134, 0.101) 50 Example 35 145 4.93 6.39 (0.134,

0.101) 53 Example 36 146 4.89 6.51 (0.134, 0.101) 57 Example 37 225 5.04 6.46 (0.134, 0.100) 56 Example 38 227 4.94 6.50 (0.134, 0.101) 52 Example 39 337 5.07 6.59 (0.134, 0.100) 51 Example 40 338 5.03 6.62 (0.134, 0.101) 50 Comparative E1 5.78 6.07 (0.134, 0.102) 44 Example 9 Comparative E2 5.70 6.09 (0.134, 0.101) 44 Example 10 Comparative E3 5.78 6.00 (0.134, 0.101) 43 Example 11 Comparative E4 5.66 6.12 (0.134, 0.100) 40 Example 12 Comparative E5 5.71 6.15 (0.134, 0.100) 45 Example 13 Comparative E6 5.68 6.07 (0.134, 0.102) 45 Example 14 Comparative E7 5.60 6.09 (0.134, 0.102) 42 Example 15 Comparative E8 5.88 5.90 (0.134, 0.101) 48 Example 16

(226) As seen from the results of Table 5, the organic light emitting device using the hole blocking layer material of the blue organic light emitting device of the present disclosure had lower driving voltage and significantly improved light emission efficiency and lifetime compared to Comparative Examples 9 to 16. Such results are due to the fact that, when holes pass through an electron transfer layer and reach a cathode without binding in a light emitting layer, efficiency and lifetime decrease in an OLED.

(227) When using a compound having a deep HOMO level as a hole blocking layer in order to prevent such a phenomenon, the holes trying to pass through the light emitting layer and reach the cathode are blocked by an energy barrier of the hole blocking layer. As a result, it is considered that probability of the holes and electrons forming excitons increases, and possibility of being emitted as light increases, and the compound of the present disclosure brings excellence in all aspects of driving, efficiency and lifetime.

Claims

1. A heterocyclic compound represented by the following Chemical Formula 1: ##STR00186## wherein, in Chemical Formula 1, R1 and R2 are the same as or different from each other, and each independently a substituted or unsubstituted C1 to C60 alkyl group; or a substituted or unsubstituted C6 to C60 aryl group; or groups adjacent to each other bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring; L1 is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group; X1 to X3 are the same as or different from each other, and each independently N; or CRa, and at least one thereof is N; Ra, Ar2 and Ar4 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R''; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group, or two or more groups adjacent to each other bond to each other to form a substituted or unsubstituted C6 to C60 aromatic hydrocarbon ring or a substituted or unsubstituted C2 to C60 heteroring; R3 to R11 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; deuterium; a halogen group; and —CN; R, R' and R'' are the same as or different from each other, and each independently hydrogen; a substituted or unsubstituted C1 to C40 alkyl group; or a substituted or unsubstituted C6 to C40 aryl group; and m is an integer of 1 to 6, and when m is 2 or greater, substituents in the parentheses are the same as or different from each other.

2. The heterocyclic compound of claim 1, wherein L1 is any one of the following structural formulae: ##STR00187## in the structural formulae, ##STR00188## means a position linked to the substituents of Chemical Formula 1; R12 is a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —CN; or —P(=O)RR'; and R and R' have the same definitions as in Chemical Formula 1.

3. The heterocyclic compound of claim 1, wherein Chemical Formula 1 is represented by any one of the following Chemical Formula 2 to Chemical Formula 4: ##STR00189## in Chemical Formulae 2 to 4, X1 to X3, R3 to R11, L1, Ar2, Ar4 and m have the same definitions as in Chemical Formula 1.
4. The heterocyclic compound of claim 1, wherein ##STR00190## of Chemical Formula 1 is represented by any one of the following Chemical Formulae 1-1 to 1-5: ##STR00191## in Chemical Formulae 1-1 to 1-5, ##STR00192## means a position linked to L1 of Chemical Formula 1; Ar11 to Ar15 are the same as or different from each other, and each independently selected from the group consisting of hydrogen; a substituted or unsubstituted C1 to C60 alkyl group; a substituted or unsubstituted C6 to C60 aryl group; a substituted or unsubstituted C2 to C60 heteroaryl group; —SiRR'R"; —P(=O)RR'; and an amine group unsubstituted or substituted with a substituted or unsubstituted C1 to C60 alkyl group, a substituted or unsubstituted C6 to C60 aryl group or a substituted or unsubstituted C2 to C60 heteroaryl group; and R, R' and R" have the same definitions as in Chemical Formula 1.
5. The heterocyclic compound of claim 1, wherein ##STR00193## of Chemical Formula 1 is represented by the following Chemical Formula 1-6 or 1-7: ##STR00194## in Chemical Formulae 1-6 and 1-7, ##STR00195## means a position linked to L1 of Chemical Formula 1; and R21 is hydrogen; a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group.
6. The heterocyclic compound of claim 4, wherein Ar12 is represented by ##STR00196## and Ar14 is a substituted or unsubstituted C6 to C60 aryl group; L2 is a direct bond; a substituted or unsubstituted C6 to C60 arylene group; or a substituted or unsubstituted C2 to C60 heteroarylene group; Z2 is a substituted or unsubstituted C6 to C60 aryl group; or a substituted or unsubstituted C2 to C60 heteroaryl group; and a and b are the same as or different from each other and each an integer of 1 to 6, and when a and b are 2 or greater, substituents in the parentheses are the same as or different from each other.
7. The heterocyclic compound of claim 1, wherein Chemical Formula 1 is represented by any one of the following compounds: ##STR00197## ##STR00198## ##STR00199## ##STR00200## ##STR00201## ##STR00202## ##STR00203## ##STR00204## ##STR00205## ##STR00206## ##STR00207## ##STR00208## ##STR00209## ##STR00210## ##STR00211## ##STR00212## ##STR00213## ##STR00214## ##STR00215## ##STR00216## ##STR00217## ##STR00218## ##STR00219## ##STR00220## ##STR00221## ##STR00222## ##STR00223## ##STR00224## ##STR00225## ##STR00226## ##STR00227## ##STR00228## ##STR00229## ##STR00230## ##STR00231## ##STR00232## ##STR00233## ##STR00234## ##STR00235## ##STR00236## ##STR00237## ##STR00238## ##STR00239## ##STR00240## ##STR00241## ##STR00242## ##STR00243## ##STR00244## ##STR00245## ##STR00246## ##STR00247## ##STR00248## ##STR00249## ##STR00250## ##STR00251## ##STR00252## ##STR00253## ##STR00254## ##STR00255## ##STR00256## ##STR00257## ##STR00258## ##STR00259## ##STR00260## ##STR00261## ##STR00262## ##STR00263## ##STR00264## ##STR00265## ##STR00266## ##STR00267## ##STR00268## ##STR00269## ##STR00270## ##STR00271## ##STR00272## ##STR00273## ##STR00274## ##STR00275## ##STR00276## ##STR00277## ##STR00278## ##STR00279## ##STR00280## ##STR00281## ##STR00282## ##STR00283## ##STR00284## ##STR00285## ##STR00286## ##STR00287## ##STR00288## ##STR00289## ##STR00290## ##STR00291## ##STR00292## ##STR00293## ##STR00294## ##STR00295## ##STR00296## ##STR00297## ##STR00298## ##STR00299## ##STR00300## ##STR00301## ##STR00302## ##STR00303## ##STR00304## ##STR00305## ##STR00306## ##STR00307## ##STR00308## ##STR00309## ##STR00310## ##STR00311## ##STR00312## ##STR00313## ##STR00314##
8. An organic light emitting device comprising: a first electrode; a second electrode provided opposite to the first electrode; and one or more organic material layers provided between the first electrode and the second electrode, wherein one or more layers of the organic material layers

comprise the heterocyclic compound of claim 1.

9. The organic light emitting device of claim 8, wherein the organic material layer comprises an electron transfer layer, and the electron transfer layer comprises the heterocyclic compound.

10. The organic light emitting device of claim 8, wherein the organic material layer comprises an electron injection layer or a hole transfer layer, and the electron injection layer or the hole transfer layer comprises the heterocyclic compound.

11. The organic light emitting device of claim 8, wherein the organic material layer comprises an electron blocking layer or a hole blocking layer, and the electron blocking layer or the hole blocking layer comprises the heterocyclic compound.

12. The organic light emitting device of claim 8, further comprising one, two or more layers selected from the group consisting of a light emitting layer, a hole injection layer, a hole transfer layer, an electron injection layer, an electron transfer layer, an electron blocking layer and a hole blocking layer.

13. The organic light emitting device of claim 8 comprising: a first electrode a first stack provided on the first electrode and comprising a first light emitting layer; a charge generation layer provided on the first stack; a second stack provided on the charge generation layer and comprising a second light emitting layer; and a second electrode provided on the second stack.

14. The organic light emitting device of claim 13, wherein the charge generation layer comprises the heterocyclic compound.
