

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12410523

Kind Code

B1

Date of Patent

September 09, 2025

Inventor(s)

Kwon; Shinjae et al.

Integrated low k recovery and ALD metal deposition process for advanced technology node

Abstract

In some embodiments, a method includes positioning a substrate within a processing chamber. The substrate includes a first low-k film having a first water contact angle. The first low-k film is disposed over an interconnect structure. The method further includes cleaning the substrate within the processing chamber to form a cleaned substrate. The cleaned substrate includes a damaged low-k film having a second water contact angle. The method further includes exposing the cleaned substrate to a recovery precursor to form a recovered substrate. The recovered substrate includes a recovered low-k film. The method further includes exposing the recovered substrate to a UV light source to form a treated substrate. The treated substrate includes a treated low-k film having a third water contact angle. The method further includes depositing a liner layer over the treated substrate via atomic layer deposition (ALD).

Inventors: Kwon; Shinjae (Santa Clara, CA), Lu; Xinyi (Santa Clara, CA), Kim; Fredrick (Santa Clara, CA), Xie; Bo (San Jose, CA), Lang; Chi-I (Cupertino, CA), Xia; Li-Qun (Santa Clara, CA), Wang; Han (Palo Alto, CA)

Applicant: Applied Materials, Inc. (Santa Clara, CA)

Family ID: 96950362

Assignee: Applied Materials, Inc. (Santa Clara, CA)

Appl. No.: 18/774617

Filed: July 16, 2024

Related U.S. Application Data

us-provisional-application US 63571672 20240329

Publication Classification

Int. Cl.: C23C16/48 (20060101); C23C16/02 (20060101); C23C16/34 (20060101); C23C16/455 (20060101); H01L21/02 (20060101)

U.S. Cl.:

CPC C23C16/482 (20130101); C23C16/0227 (20130101); C23C16/34 (20130101); C23C16/45525 (20130101); H01L21/0206 (20130101); H01L21/02277 (20130101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2006/0254374	12/2005	Baklanov	257/E21.531	G01N 21/211
2007/0077768	12/2006	Fujii	257/E21.255	H01L 21/76826
2007/0249164	12/2006	Chen	438/638	H01L 21/76813
2009/0068768	12/2008	Urbanowicz	257/E21.53	G01N 21/71
2009/0179003	12/2008	Nishimura	216/41	H01L 21/76826
2016/0247695	12/2015	Niskanen	N/A	H01L 21/02334

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
WO 2014/011364	12/2013	WO	H01L 21/31

Primary Examiner: Salerno; Sarah K

Attorney, Agent or Firm: Patterson + Sheridan, LLP

Background/Summary

FIELD

(1) Embodiments described herein generally relate to processing low-k dielectric films. More specifically, embodiments described herein relate to processes for repairing low-k dielectric films and depositing metal layers thereon.

BACKGROUND

(2) The dielectric constant (k) of dielectric films in semiconductor fabrication is continually decreasing as device scaling continues. Minimizing integration damage on low dielectric constant (low-k) films is beneficial to be able to continue decreasing feature sizes. Unfortunately, damage incurred to low-k films through various processes can cause increases in dielectric constant and surface hydrophilicity, both of which can result in decreased device performance (e.g., potential failure of an integrated circuit).

(3) Efforts have been directed towards developing processes designed to recover properties lost due to accrued damage to the low-k film. However, the resulting properties of low-k films subjected to such processes may not allow subsequent processing and deposition operations. In many instances, low-k films having undergone a dielectric constant recovery process exhibit undesirable surface

properties which are unfavorable for subsequent atomic layer deposition processes.

(4) Thus, there is a need for improved processes for dielectric constant recovery.

SUMMARY

(5) Embodiments described herein generally relate to processes for processing low-k dielectric films. More specifically, embodiments described herein relate to processes for repairing low-k dielectric films and depositing metal layers thereon.

(6) In some embodiments, a method includes positioning a substrate within a processing chamber. The substrate includes a first low-k film having a first water contact angle. The first low-k film is disposed over an interconnect structure. The method further includes cleaning the substrate within the processing chamber to form a cleaned substrate. The cleaned substrate includes a damaged low-k film having a second water contact angle. The damaged low-k film is a product of the first low-k film. The method further includes exposing the cleaned substrate to a recovery precursor to form a recovered substrate. The recovered substrate includes a recovered low-k film. The recovered low-k film is a product of the damaged low-k film. The method further includes exposing the recovered substrate to a UV light source to form a treated substrate. The treated substrate includes a treated low-k film having a third water contact angle. The treated low-k film is a product of the recovered low-k film. The method further includes depositing a liner layer over the treated substrate via atomic layer deposition (ALD).

(7) In some embodiments, a method includes positioning a substrate within a processing chamber. The substrate includes a first low-k film having a first water contact angle. The first low-k film is disposed over an interconnect structure. The method further includes cleaning the substrate within the processing chamber to form a cleaned substrate. The cleaned substrate includes a damaged low-k film having a second water contact angle. The damaged low-k film is a product of the first low-k film. The method further includes exposing the cleaned substrate to a UV light source to form a treated substrate. The treated substrate includes a treated low-k film having a third water contact angle. The treated low-k film is a product of the damaged low-k film. The method further includes exposing the treated substrate to a recovery precursor to form a recovered substrate. The recovered substrate includes a recovered low-k film. The recovered low-k film is a product of the treated low-k film. The method further includes depositing a liner layer over the recovered substrate via atomic layer deposition (ALD).

(8) In some embodiments, a method includes positioning a substrate within a processing chamber. The substrate includes a first low-k film having a first water contact angle. The first low-k film is disposed over an interconnect structure. The method further includes cleaning the substrate within the processing chamber to form a cleaned substrate. The cleaned substrate includes a damaged low-k film having a second water contact angle. The damaged low-k film is a product of the first low-k film. The method further includes exposing the cleaned substrate to a recovery precursor to form a recovered substrate. The recovered substrate includes a recovered low-k film. The recovered low-k film is a product of the damaged low-k film. The method further includes exposing the recovered substrate to a UV light source to form a treated substrate. The treated substrate includes a treated low-k film having a third water contact angle. The treated low-k film is a product of the recovered low-k film. The method further includes depositing a liner layer over the treated substrate via atomic layer deposition (ALD). The first water contact angle is greater than the second water contact angle, and the second water contact angle is less than the third water contact angle.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) So that the manner in which the above recited features of the present disclosure can be understood in detail, a more particular description of the disclosure, briefly summarized above,

may be had by reference to embodiments, some of which are illustrated in the appended drawings. It is to be noted, however, that the appended drawings illustrate only typical embodiments of this disclosure and are therefore not to be considered limiting of scope, for the disclosure may admit to other equally effective embodiments.

(2) FIG. 1 is a schematic cross-sectional view of a process chamber, according to one or more embodiments.

(3) FIG. 2 is a schematic block diagram of a method of substrate processing, according to one or more embodiments.

(4) FIG. 3A is a partial schematic side cross-sectional views of an interconnect structure during a method, according to one or more embodiments.

(5) FIG. 3B is a partial schematic side cross-sectional views of an interconnect structure during a method, according to one or more embodiments.

(6) FIG. 3C is a partial schematic side cross-sectional views of an interconnect structure during a method, according to one or more embodiments.

(7) FIG. 3D is a partial schematic side cross-sectional views of an interconnect structure during a method, according to one or more embodiments.

(8) FIG. 4A is a molecular representation of a low-k film during a method, according to one or more embodiments.

(9) FIG. 4B is a molecular representation of a low-k film during a method, according to one or more embodiments.

(10) FIG. 4C is a molecular representation of a low-k film during a method, according to one or more embodiments.

(11) FIG. 5 is a schematic block diagram of a method of substrate processing, according to one or more embodiments.

(12) FIG. 6 is a schematic block diagram of a method of substrate processing, according to one or more embodiments.

(13) FIG. 7 is a schematic block diagram of a method of substrate processing, according to one or more embodiments.

(14) FIG. 8 is a schematic block diagram of a method of substrate processing, according to one or more embodiments.

(15) FIG. 9 is a series of surface images of an interconnect structure after a method, according to one or more embodiments.

DETAILED DESCRIPTION

(16) The present disclosure provides methods to recover properties of low-k films that were damaged during substrate processing procedures. Recovery processes disclosed herein generally include a series of sequential property recovery operations including exposing the substrate to one or more recovery precursors and exposing the substrate to a UV light source. Recovery processes disclosed herein can reduce elevated k values of damaged low-k films, and also increase surface hydrophobicity of such films. Additionally, the sequential recovery processes of the present disclosure provide a balance between the recovery of low-k values and recovery of hydrophilic/hydrophobic properties such that the surface of the resulting films are favorable for subsequent ALD metal film deposition.

(17) FIG. 1 is a schematic cross-sectional view of a process chamber **100**, according to one or more embodiments. The process chamber **100** may be a vapor deposition chamber that includes UV radiation for assisting a silylation reaction. In one or more embodiments, the process chamber **100** may be the ONYX® or the SILENA® process chamber available from Applied Materials, Inc., of Santa Clara, California. The process chamber **100** includes a chamber body **102** and a chamber lid **104** disposed over the chamber body **102**. The chamber body **102** and the chamber lid **104** form an inner volume **106**. A substrate support assembly **108** is disposed in the inner volume **106**. The substrate support assembly **108** may receive and support a substrate **110** thereon for processing.

(18) A first UV transparent gas distribution showerhead **116** may be hung in the inner volume **106** through a central opening **112** of the chamber lid **104** by an upper clamping member **118** and a lower clamping member **120**. The UV transparent gas distribution showerhead **116** may be positioned facing the substrate support assembly **108** to distribute one or more processing gases across a distribution volume **122**, which is below the first UV transparent gas distribution showerhead **116**. A second UV transparent gas showerhead **124** may be hung in the inner volume **106** through the central opening **112** of the chamber lid **104** below the first UV transparent gas distribution showerhead **116**. Each of the UV transparent gas distribution showerheads **116**, **124** may be disposed in a recess formed in the chamber lid **104**. A first recess **126** may be an annular recess around an internal surface of the chamber lid **104**, and the first UV transparent gas distribution showerhead **116** fits into the first recess **126**. Likewise, a second recess **128** may receive the second UV transparent gas distribution showerhead **124**.

(19) A UV transparent window **114** may be disposed above the first UV transparent gas distribution showerhead **116**. The UV transparent window **114** may be positioned above the first UV transparent gas distribution showerhead **116** forming a gas volume **130** between the UV transparent window **114** and the first UV transparent gas distribution showerhead **116**. The UV transparent window **114** may be secured to the chamber lid **104** by any means, such as clamps, screws, bolts, etc.

(20) The UV transparent window **114** and the first and second UV transparent gas distribution showerheads **116**, **124** may be at least partially transparent to thermal or radiant energy within the UV wavelengths. The UV transparent window **114** may be quartz or another UV transparent material, such as sapphire, CaF₂, MgF₂, AlON, a silicon oxide material, a silicon oxynitride material, or another transparent material.

(21) A UV source **150** may be disposed above the UV transparent window **114**. The UV source **150** may be configured to generate UV energy and project the UV energy towards the substrate support assembly **108** through the UV transparent window **114**, the first UV transparent gas distribution showerhead **116**, and the second UV transparent gas distribution showerhead **124**, thereby exposing the substrate **110** on the substrate support assembly **108** to UV light. A cover (not shown) may be disposed above the UV source **150**. In one or more embodiments, the cover may be shaped to assist the projection of the UV energy from the UV source **150** towards the substrate support.

(22) In one or more embodiments, the UV source **150** may include one or more UV lights **152** to generate UV radiation. The UV lights **152** may be lamps, LED emitters, or other UV emitters. In one or more embodiments, the UV lights **152** may be argon lamps discharging radiation at 126 nm, krypton lamps discharging at 146 nm, xenon lamps discharging at 172 nm, krypton chloride lamps discharging at 222 nm, xenon chloride lamps discharging at 308 nm, mercury lamps discharging at 254 nm or 365 nm, metal vapor lamps such as zinc discharging at 214 nm, rare earth near-UV lamps such as europium-doped strontium borate or fluoroborate lamps discharging at 368-371 nm, to name a few examples.

(23) The process chamber **100** may include flow channels **132**, **134**, **136** configured to supply one or more processing gases across the substrate support assembly **108** to process a substrate **110** disposed thereon. A first flow channel **132** provides a flow pathway for gas to enter the gas volume **130** and to be exposed to UV radiation from the UV source **150**. The gas from the gas volume **130** may flow through the first UV transparent gas distribution showerhead **116** into the distribution volume **122**. A second flow channel **134** may provide a flow pathway for precursor compounds and gases to enter the distribution volume **122** directly without passing through the first UV transparent gas distribution showerhead **116** to mix with the gas that was previously exposed to UV radiation in the gas volume **130**. The mixed gases in the distribution volume **122** may be further exposed to UV radiation through the first UV transparent gas distribution showerhead **116** before flowing through the second UV transparent gas distribution showerhead **124** into a space proximate the substrate support assembly **108**. The gas proximate the substrate support assembly **108**, and a substrate

disposed on the substrate support assembly **108**, is further exposed to the UV radiation through the second UV transparent gas distribution showerhead **124**. Purge gases may be provided through an opening **138** in the bottom of the process chamber **100** such that the purge gas flow around the substrate support assembly **108**, preventing intrusion of processing gases into the space under the substrate support assembly **108**. One or more gases may be exhausted through the opening **138**.

(24) The first UV transparent gas distribution showerhead **116** may include a plurality of holes **140** that allow processing gas to flow from the gas volume **130** to the distribution volume **122**. The second UV transparent gas distribution showerhead **124** may also include a plurality of holes **142** that allow processing gas to flow from the distribution volume **122** into the processing space proximate the substrate support assembly **108**. The holes **140**, **142** in the first and second UV transparent gas distribution showerheads **116**, **124** may be evenly distributed or irregularly spaced.

(25) A purge gas or carrier gas source **154** may be coupled to the first flow channel **132** through a conduit **156**. Purge gas from the purge gas source **154** may be provided through the first flow channel **132** during substrate processing to prevent intrusion of process gases into the gas volume **130**. A cleaning gas source **174** may also be coupled to the first flow channel **132** through the conduit **156** to provide cleaning of the conduit **156**, the first flow channel **132**, the gas volume **130**, and the rest of the chamber body **102** when not processing substrates.

(26) A process gas or precursor compound source **158** may be coupled to the second flow channel **134** through a conduit **160** to provide a mixture, as described above, to the chamber body **102**. The process gas source **158** may also be coupled to a third flow channel **136**. Appropriate valves may allow selection of one or both of the flow channels **134**, **136** for flowing the process gas mixture into the chamber body **102**.

(27) Substrate temperature may be controlled by providing heating and cooling features in the substrate support assembly **108**. A coolant conduit **164** may be coupled to a coolant source **170** to provide a coolant to a cooling plenum **162** disposed in the substrate support assembly **108**. One example of a coolant that may be used is a mixture of 50% ethylene glycol in water, by volume. The coolant flow is controlled to maintain temperature of the substrate at or below a desired level to promote deposition of UV-activated oligomers or fragments on the substrate. A heating element **166** may also be provided in the substrate support assembly **108**. The heating element **166** may be a resistive heater, and may be coupled to a heating source **172**, such as a power supply, by a conduit **168**. The heating element **166** may be used to heat the substrate during the hardening process described above.

(28) FIG. 2 is a schematic block diagram of a method **200** of substrate processing, according to one or more embodiments. FIGS. 3A-3D are partial schematic side cross-sectional views of an interconnect structure **300A-300D** during the method **200**, according to one or more embodiments. FIGS. 4A-4C are molecular views of a low-k film **302a**, **302b**, and **302c** during the method **200**, according to one or more embodiments.

(29) At operation **210**, a substrate, which may include an interconnect structure **300A** shown in FIG. 3A, is transferred into a process chamber. The process chamber may be a deposition process chamber such as the process chamber **100** depicted in FIG. 1. At operation **210**, the interconnect structure **300A** is a post-deposition interconnect structure. In other words, the interconnect structure **300A** includes a low-k film deposited thereon prior to operation **210**. The interconnect structure **300A**, shown in FIG. 3A may include a low-k film **302a** on an etch stop layer **304**, a metal barrier **306** between the etch stop layer **304** and a copper layer **310**, a metal barrier **306** between the copper layer **310** and a substrate **308**, residue **314** on the copper layer **310**, and residue **314** on the low-k film **302a**. The interconnect structure **300A** may also include an intermediate layer **312** between the substrate **308** and the etch stop layer **304**. In some embodiments, an interconnect structure with a different configuration than that shown in FIG. 3A may be utilized in method **200**.

(30) FIG. 4A is a molecular view of the low-k film **302a** at operation **210**. In FIG. 4A, the low-k film **302a** has Si—O bonds, Si—CH₃ bonds, and Si—H bonds. In some embodiments, the



metal barrier **306** may comprise tantalum nitride (TaN), hafnium oxide (HfO₂), aluminum oxide (AlO_x), zirconium oxide (ZrO₂), titanium nitride (TiN), nickel oxide (NiO), nickel nitride (NiN), and combinations thereof.

(31) At operation **220**, the interconnect structure **300A** is cleaned in the process chamber, such as process chamber **100**. As a result of operation **220**, the low-k film **302a** of the interconnect structure **300A** can become damaged. As shown in FIGS. **4A** and **4B**, the overall number of Si—CH₃ bonds initially present in the low-k film **302a** may be decreased and Si—OH bonds may be formed, resulting in the low-k film **302b**. With the increase of Si—OH bonds, the low-k film **302b** becomes more hydrophilic relative to the low-k film **302a**, which is undesirable. The decrease in Si—CH₃ bonds in the low-k film **302b** results in an increased k value of the low-k film **302b**, relative to the initial k value of the low-k film **302a**. In some embodiments, the cleaning operations of operation **220** may include etching, ash, wet cleaning operations, or combinations thereof.

(32) In at least one embodiment, the cleaning operations of operation **220** can include a plasma etch treatment process. In one exemplary embodiment, a process pressure in the processing chamber **100** is regulated between about 10 mTorr to about 5000 mTorr, such as about 10 mTorr and about 400 mTorr, such as about 200 mTorr. A RF bias power at a frequency of about 13 MHz may be applied to maintain a plasma in the treatment gas mixture (e.g., a hydrogen containing gas, such as diatomic hydrogen). For example, a RF bias power of less than 100 Watts, such as about 5 Watts to about 50 Watts may be applied to maintain a plasma inside the processing chamber **100**. The treatment gas mixture may be flowed into the chamber at a rate of about 100 sccm to about 800 sccm. The interconnect structure **300A** is maintained at a temperature of about 25° C. to about 300° C., such as about 50° C. to about 140° C., such as about 50° C. to about 130° C., such as about 110° C. to about 125° C. The interconnect structure **300A** may be subjected to the cleaning operations of operation **220** for about 5 second to about 300 second, such as about 30 seconds to about 90 seconds.

(33) At operation **230**, the interconnect structure **300B** is subjected to a post-treatment process, where the low-k film **302b** of the interconnect structure **300B** is repaired. As such, the k value of the low-k film **302c** of the interconnect structure **300C** decreases in comparison to the k value of the low-k film **302b**. Furthermore, the hydrophobicity of the low-k film **302c** increases relative to the hydrophobicity of the low-k film **302b**, as a result of the repaired chemical structure of the low-k film **302c**. Operation **230** may be performed in the same chamber as operation **220**, or may be performed in a different chamber. As shown in FIG. **4C**, the low-k film **302c** has fewer to no Si—OH bonds and a greater percentage of Si—CH₃ bonds than low-k films **302a** and/or **302b** shown in FIG. **3A** and FIG. **3B**, respectively. In conventional repair processes, low-k films which have undergone a dielectric constant recovery process exhibit hydrophobic surface properties which are unfavorable for subsequent atomic layer deposition processes. However, aspects of this disclosure result in more favorable (e.g., less hydrophobic) surface properties.

(34) In some embodiments, operation **230** may include exposing the low-k film **302b** of the interconnect structure **300B** to a recovery precursor, an ultraviolet (UV) light source, or a combination thereof. In some embodiments, operation **230** includes the removal of the Si—OH bonds of the low-k film **302b** and the formation of the Si—O—Si bonds of the low-k film **302c**. Without being bound by theory, such chemical reactions may be performed via reaction schemes (1) and (2) shown below. Chemical reactions of schemes (1) and (2) illustrate the removal of the Si—OH bonds and the formation of the Si—CH₃ bonds when the low-k film **302b** is exposed to a recovery precursor.



(35) In some embodiments, operation **230** may also be performed utilizing UV light, for example,

the interconnect structure **300B** may be exposed to UV light during operation **230**.

(36) At operation **240**, and as shown in FIGS. **3C** and **3D**, the interconnect structure **300C** is subjected to a liner deposition process where a liner layer **316** is disposed over the surface of the interconnect structure **300C** including, at least, the low-k film **302c** and/or the surface of the copper layer **310** to form the interconnect structure **300D**. The liner layer **316** of the interconnect structure **300D** may be deposited by any suitable deposition method, such as atomic layer deposition (ALD), chemical vapor deposition (CVD), high pressure CVD (HPCVD), high density plasma CVD, remote plasma CVD, microwave assisted CVD, NBECVD or plasma enhanced atomic layer deposition (PEALD) where the terms ALD, CVD, HPCVD, NBECVD, PEALD refer to the sequential introduction of reactants or precursors to deposit a layer over a substrate structure, or any other suitable deposition process. In at least one embodiment, the liner layer **316** of the interconnect structure **300D** is a metal liner deposited by an ALD process, such as TaN and/or HfO.sub.2.

(37) In some embodiments, operation **240** includes depositing a liner layer **316** over the interconnect structure **300C** via an ALD process. The ALD process may be conducted in a process chamber, such as the process chamber **100** depicted in FIG. **1**. In at least one embodiment, the ALD process includes exposing the interconnect structure **300C** to a metal precursor and a reactant (e.g., an alcohol and/or ammonia gas) to form a metal layer thereon. The metal precursor may include one or more of aluminum, hafnium, zirconium, nickel, zinc, tantalum, or titanium. The metal precursor may also include a carbo ligand, an amino ligand, a halide ligand, or a combination thereof.

(38) The temperature of the interconnect structure **300C** during the ALD process can be any suitable temperature depending on, for example, the precursor(s) being used. During processing, the interconnect structure **300C** can be heated or cooled. Such heating or cooling can be accomplished by any suitable means. In some embodiments, the interconnect structure **300C** is maintained at a temperature greater than or equal to about 25° C., or about 50° C., or about 100° C., or about 150° C., or about 200° C., or about 250° C., or about 300° C., or about 350° C., or about 400° C., or about 450° C., or about 500° C. In some embodiments, the interconnect structure **300C** temperature is maintained at a temperature less than or equal to about 600° C., or about 550° C., or about 500° C., or about 450° C., or about 400° C., or about 350° C., or about 300° C., or about 250° C., or about 200° C., or about 150° C., or about 100° C., or about 50° C., or about 25° C. In some embodiments, the interconnect structure **300C** temperature is maintained at a temperature of about 350° C.

(39) The metal precursor and reactant may be provided to the processing chamber. The flow rate of the metal precursor and reactant can be any suitable flow rate such as about 1 sccm to about 5000 sccm, such as about 200 sccm to about 4000 sccm, such as about 300 sccm to about 3000 sccm, such as about 5000 sccm to about 2000 sccm. The metal precursor and reactant can be provided at any suitable pressure such as about 5 mTorr to about 25 Torr, such as about 100 mTorr to about 20 Torr, such as about 5 Torr to about 20 Torr, such as about 50 mTorr to about 2000 mTorr, such as about 100 mTorr to about 1000 mTorr, such as about 200 mTorr to about 500 mTorr.

(40) The period of time that the interconnect structure **300C** is exposed to metal precursor and reactant may be any suitable amount of time necessary to allow for an adequate nucleation layer to form over the surface of the interconnect structure **300C**. The interconnect structure **300C** may be exposed to the metal precursor and reactant for about 0.1 seconds to about 90 seconds, such as about 0.5 seconds to about 60 seconds, such as about 1 second to about 30 seconds, such as about 2 seconds to about 25 seconds, such as about 3 seconds to about 20 seconds, such as about 4 seconds to about 15 seconds, such as about 5 seconds to about 10 seconds.

(41) In some embodiments, an inert gas may additionally be provided to the process chamber at the same time as the metal precursor and reactant. The inert gas may be flowed into the processing chamber at a constant flow rate of about 1 sccm to about 10000 sccm. The inert gas may be any

inert gas, such as argon, helium, neon, combinations thereof, or the like.

(42) In some embodiments, the process chamber is maintained at a pressure of about 0.2 Torr to about 100 Torr throughout the ALD process, such as about 0.3 Torr to about 90 Torr, such as about 0.5 Torr to about 80 Torr, such as about 1 Torr to about 50 Torr. The processing chamber pressure during deposition can be about 50 mTorr to 750 Torr, such as about 100 mTorr to about 400 Torr, such as about 1 Torr to about 100 Torr, such as about 2 Torr to about 10 Torr.

(43) In some embodiments, the resulting liner layer **316** of the interconnect structure **300D** has a thickness of about 1200 Å to about 1300 Å, such as about 1225 Å to about 1275 Å, such as about 1240 Å to about 1260 Å, alternatively about 1200 Å to about 1225 Å, alternatively about 1225 Å to about 1240 Å, alternatively about 1260 Å to about 1275 Å, alternatively about 1275 Å to about 1300 Å.

(44) FIG. 5 is a schematic block diagram of a method **500** of substrate processing, according to one or more embodiments. Similar to the method **200**, at operation **210**, a substrate, such as a wafer having an interconnect structure **300A** shown in FIG. 3A, is transferred into a process chamber. The process chamber may be a deposition process chamber such as the process chamber **100** depicted in FIG. 1. At operation **210**, the interconnect structure **300A** is a post-deposition interconnect structure. In other words, the interconnect structure **300A** includes a low-k film deposited thereon prior to operation **210**. At operation **220**, the interconnect structure **300A** is cleaned in the process chamber **100**. As previously discussed, the cleaning operations of operation **220** can damage the chemical composition of the low-k film **302a** of interconnect structure **300A**, resulting in the increased hydrophilicity and increased k values of the low-k film **302b** of the interconnect structure **300B**.

(45) At operation **510**, the interconnect structure **300B** is subjected to a post-treatment process, where the low-k film **302b** of the interconnect structure **300B** is repaired via exposure to a recovery precursor resulting in the low-k film **302c** of the interconnect structure **300C**. A recovery precursor can be an aminosilane. For example, the recovery precursor may include a molecule selected from Group 1. In Group 1, each R may be independently selected from methyl, ethyl, isopropyl, tert-butyl, and H. Each R' may be independently selected from an alkane, an alkene, and an alkyne. Each R' may independently include one to twenty carbon atoms, such as 2 to 10 carbon atoms, such as 3 to 5 carbon atoms.

(46) ##STR00001##

(47) In one or more embodiments, the recovery precursor may be one or more of the molecules pictured in Group 1 Examples below.

(48) ##STR00002##

EXAMPLES

(49) In some embodiments, the recovery precursor may include an oxysilane, such as an oxysilane selected from Group 2. In Group 2, each R may be independently selected from methyl, ethyl, isopropyl, and tert-butyl. Each R' may be independently selected from an alkyl, a cycloalkyl, an alkynyl, and an aryl. Each R' may independently include one to twenty carbon atoms, such as 2 to 10 carbon atoms, such as 3 to 5 carbon atoms.

(50) ##STR00003##

(51) In certain embodiments, the recovery precursor may include a halosilane, such as a halosilane selected from Group 3. In Group 3, each X may be independently Cl, Br, or I. Each R' may be independently selected from alkyl, a cycloalkyl, an alkynyl, and an aryl. Each R' may independently include one to twenty carbon atoms, such as 2 to 10 carbon atoms, such as 3 to 5 carbon atoms.

(52) ##STR00004##

(53) In certain embodiments, the recovery precursor may include an acetylsilane, such as an acetylsilane of Group 4. In Group 4, each R' may be independently selected from an alkyl, a cycloalkyl, an alkynyl, and an aryl. Each R may be an alkyl. Each R' may include one to twenty

carbon atoms, such as 2 to 10 carbon atoms, such as 3 to 5 carbon atoms.

(54) ##STR00005##

(55) In certain embodiments, the recovery precursor may include an ester, such as an ester selected from Group 5. In Group 5, each R and R' may be independently selected from hydrogen, alkyl, a cycloalkyl, an alkynyl, and an aryl. In embodiments where R and/or R' contain carbon atoms, each R and R' may independently include one to twenty carbon atoms, such as 2 to 10 carbon atoms, such as 3 to 5 carbon atoms.

(56) ##STR00006##

(57) In certain embodiments, the recovery precursor may include a molecule selected from Group 6. In Group 6, each R, R', and R'' may be independently selected from hydrogen, an alkane, an alkene, an alkyne, and an aryl. In embodiments where R, R', and/or R'' contain carbon, R, R', and R'' may include one to twenty carbon atoms, such as 2 to 10 carbon atoms, such as 3 to 5 carbon atoms.

(58) ##STR00007##

(59) In some embodiments, operation **510** may be performed in a processing chamber, such as the process chamber **100** depicted in FIG. **1**. In some embodiments, the recovery precursor may be introduced to the processing chamber using a precursor gas flow rate of about 100 milligrams per minute (mgm) to about 2000 mgm, such as about 250 mgm to about 1500 mgm, such as about 500 mgm to about 1000 mgm, alternatively about 100 mgm to about 250 mgm, alternatively about 250 mgm to about 500 mgm, alternatively about 1000 mgm to about 1500 mgm, alternatively about 1500 mgm to about 2000 mgm. In some embodiments, the recovery precursor may be introduced into the processing chamber with a carrier gas, such as He, Ar, N.sub.2, and combinations thereof. The carrier gas may be introduced into the processing chamber using a gas flow rate of about 1000 standard cubic centimeters per minute (sccm) to about 5000 sccm, such as about 2000 sccm to about 4000 sccm, such as about 2500 sccm to about 3500 sccm, alternatively about 1000 sccm to about 2000 sccm, alternatively about 2000 sccm to about 2500 sccm, alternatively about 3500 sccm to about 4000 sccm, alternatively about 4000 to about 5000 sccm.

(60) In one or more embodiments, the pressure within the process chamber during operation **510** may be about 3 Torr to about 100 Torr, such as about 10 Torr to about 50 Torr, such as about 25 Torr to about 35 Torr, alternatively about 3 Torr to about 10 Torr, alternatively about 10 Torr to about 25 Torr, alternatively about 35 Torr to about 50 Torr, alternatively about 50 Torr to about 100 Torr. In one or more embodiments, the temperature within the processing chamber during operation **510** may be about 75° C. to about 500° C., such as about 150° C. to about 400° C., such as about 250° C. to about 350° C., alternatively about 75° C. to about 150° C., alternatively about 150° C. to about 250° C., alternatively about 350° C. to about 400° C., alternatively about 400° C. to about 500° C. In one or more embodiments, the substrate may be exposed to the recovery precursor for about 1 min to about 10 min, such as about 2.5 min to about 7.5 min, such as about 4 min to about 6 min, alternatively about 1 min to about 2.5 min, alternatively about 2.5 min to about 4 min, alternatively about 6 min to about 7.5 min, alternatively about 7.5 min to about 10 min.

(61) Once the low-k film **302b** is repaired via exposure to the recovery precursor, the method **500** further includes operation **240**, where the interconnect structure **300C** is subjected to a liner deposition process where a liner layer **316** is disposed over the surface of the interconnect structure **300C** including, at least, the low-k film **302c** and/or the surface of the copper layer **310** to form the interconnect structure **300D**. In at least one embodiment, the liner layer **316** of the interconnect structure **300D** is a metal liner deposited by an ALD process.

(62) FIG. **6** is a schematic block diagram of a method **600** of substrate processing, according to one or more embodiments. Similar to the method **200**, at operation **210**, a substrate, such as an interconnect structure **300A** shown in FIG. **3A**, is transferred into a process chamber. The process chamber may be a deposition process chamber such as the process chamber **100** depicted in FIG. **1**. At operation **210**, the interconnect structure **300A** is a post-deposition interconnect structure. In

other words, the interconnect structure **300A** includes a low-k film deposited thereon prior to operation **210**. At operation **220**, the interconnect structure **300A** is cleaned in the process chamber **100**. As previously discussed, the cleaning operations of operation **220** can damage the low-k film **302a** of the interconnect structure **300A**, resulting in the increased hydrophilicity and increased k value of the low-k film **302b** of interconnect structure of **300B**. At operation **610**, the interconnect structure **300B** is subjected to a post-treatment process, where the low-k film **302b** of the interconnect structure **300B** is repaired via simultaneous exposure to a recovery precursor and a UV light source (e.g., UV-assisted silylation reaction).

(63) In some embodiments, operation **610** may be performed in a processing chamber, such as the process chamber **100** depicted in FIG. **1**. In some embodiments, the recovery precursor may be introduced to the processing chamber using a precursor gas flow rate of about 100 mgm to about 2000 mgm, such as about 250 mgm to about 1500 mgm, such as about 500 mgm to about 1000 mgm, alternatively about 100 mgm to about 250 mgm, alternatively about 250 mgm to about 500 mgm, alternatively about 1000 mgm to about 1500 mgm, alternatively about 1500 mgm to about 2000 mgm. In some embodiments, the recovery precursor may be introduced into the processing chamber with a carrier gas, such as He, Ar, N.sub.2, and combinations thereof. The carrier gas may be introduced into the processing chamber using a gas flow rate of about 1000 sccm to about 5000 sccm, such as about 2000 sccm to about 4000 sccm, such as about 2500 sccm to about 3500 sccm, alternatively about 1000 sccm to about 2000 sccm, alternatively about 2000 sccm to about 2500 sccm, alternatively about 3500 sccm to about 4000 sccm, alternatively about 4000 to about 5000 sccm.

(64) In one or more embodiments, the pressure within the process chamber during operation **610** may be about 3 Torr to about 100 Torr, such as about 10 Torr to about 50 Torr, such as about 25 Torr to about 35 Torr, alternatively about 3 Torr to about 10 Torr, alternatively about 10 Torr to about 25 Torr, alternatively about 35 Torr to about 50 Torr, alternatively about 50 Torr to about 100 Torr. In one or more embodiments, the temperature within the processing chamber during operation **510** may be about 75° C. to about 500° C., such as about 150° C. to about 400° C., such as about 250° C. to about 350° C., alternatively about 75° C. to about 150° C., alternatively about 150° C. to about 250° C., alternatively about 350° C. to about 400° C., alternatively about 400° C. to about 500° C. In one or more embodiments, the substrate may be exposed to the recovery precursor for about 1 min to about 10 min, such as about 2.5 min to about 7.5 min, such as about 4 min to about 6 min, alternatively about 1 min to about 2.5 min, alternatively about 2.5 min to about 4 min, alternatively about 6 min to about 7.5 min, alternatively about 7.5 min to about 10 min.

(65) In one or more embodiments, the interconnect structure **300B** may be simultaneously exposed to the UV light source throughout a portion of the time in which the substrate is exposed to the recovery precursor in operation **610**. In at least one embodiment, the interconnect structure **300B** may be simultaneously exposed to the UV light source throughout the time in which the substrate is exposed to the recovery precursor. In one or more embodiments, the interconnect structure **300B** may be exposed to a UV light source of about 600 W/in during operation **610**, such as about 400 W/in to about 800 W/in, such as about 500 W/in to about 700 W/in, alternatively about 400 W/in to about 500 W/in, alternatively about 500 W/in to about 600 W/in, alternatively about 600 W/in to about 700 W/in, alternatively about 700 W/in to about 800 W/in.

(66) Once the low-k film **302b** of interconnect structure **300B** is repaired via simultaneous exposure to the recovery precursor and UV light source to form the low-k film **302c** of interconnect structure **300C**, the method **600** further includes operation **240**, where the interconnect structure **300C** is subjected to a liner deposition process where a liner layer **316** is disposed over the surface of the interconnect structure **300C** including, at least, the low-k film **302c** and/or the surface of the copper layer **310** to form the interconnect structure **300D**. In at least one embodiment, the liner layer **316** of interconnect structure **300D** is a metal liner deposited by an ALD process.

(67) FIG. **7** is a schematic block diagram of a method **700** of substrate processing, according to one

or more embodiments. Similar to the method **200** of FIG. 2, at operation **210** of FIG. 7, a substrate, such as an interconnect structure **300A** shown in FIG. 3A, is transferred into a process chamber. The process chamber may be a deposition process chamber such as the process chamber **100** depicted in FIG. 1. At operation **210**, the interconnect structure **300A** is a post-deposition interconnect structure. In other words, the interconnect structure **300A** includes a low-k film deposited thereon prior to operation **210**. At operation **220**, the interconnect structure **300A** is cleaned in the process chamber **100**. As previously discussed, the cleaning operations of operation **220** can damage the low-k film **302a** of the interconnect structure **300A**, resulting in the increased hydrophilicity and increased k values of the low-k film **302b** of the interconnect structure **300B**. At operation **510**, the low-k film **302b** of the interconnect structure **300B** is repaired via exposure to a recovery precursor.

(68) At operation **710**, interconnect structure **300B** is subsequently subjected to additional UV treatment with via exposure to a UV light source. In some embodiments, operation **710** may be performed in a processing chamber, such as the process chamber **100** depicted in FIG. 1. In one or more embodiments, the interconnect structure **300B** may be exposed to a UV light source of about 600 W/in during operation **710**, such as about 400 W/in to about 800 W/in, such as about 500 W/in to about 700 W/in, alternatively about 400 W/in to about 500 W/in, alternatively about 500 W/in to about 600 W/in, alternatively about 600 W/in to about 700 W/in, alternatively about 700 W/in to about 800 W/in. In one or more embodiments, the interconnect structure **300B** may be exposed to the UV light source for about 1 second(s) to about 60 minutes (min) during operation **710**, such as about 1 s to about 30 min, such as about 1 s to about 10 min.

(69) In one or more embodiments, the pressure within the process chamber during operation **710** may be about 3 Torr to about 100 Torr, such as about 10 Torr to about 50 Torr, such as about 25 Torr to about 35 Torr, alternatively about 3 Torr to about 10 Torr, alternatively about 10 Torr to about 25 Torr, alternatively about 35 Torr to about 50 Torr, alternatively about 50 Torr to about 100 Torr. In one or more embodiments, the temperature within the processing chamber during operation **510** may be about 75° C. to about 500° C., such as about 150° C. to about 400° C., such as about 250° C. to about 350° C., alternatively about 75° C. to about 150° C., alternatively about 150° C. to about 250° C., alternatively about 350° C. to about 400° C., alternatively about 400° C. to about 500° C. In one or more embodiments, the substrate may be exposed to the recovery precursor for about 1 min to about 10 min, such as about 2.5 min to about 7.5 min, such as about 4 min to about 6 min, alternatively about 1 min to about 2.5 min, alternatively about 2.5 min to about 4 min, alternatively about 6 min to about 7.5 min, alternatively about 7.5 min to about 10 min.

(70) At operation **240**, the interconnect structure **300C** is subjected to a liner deposition process where a liner layer **316** is disposed over the surface of the interconnect structure **300C** including, at least, the low-k film **302c** and/or the surface of the copper layer **310** to form the interconnect structure **300D**. In at least one embodiment, the liner layer **316** of the interconnect structure **300D** is a metal liner deposited by an ALD process.

(71) FIG. 8 is a schematic block diagram of a method **800** of substrate processing, according to one or more embodiments. Similar to the method **200** of FIG. 2, at operation **210** of FIG. 8, a substrate, such as an interconnect structure **300A** shown in FIG. 3A, is transferred into a process chamber. The process chamber may be a deposition process chamber such as the process chamber **100** depicted in FIG. 1. At operation **210**, the interconnect structure **300A** is a post-deposition interconnect structure. In other words, the interconnect structure **300A** includes a low-k film deposited thereon prior to operation **210**. At operation **220**, the interconnect structure **300A** is cleaned in the process chamber **100**. As previously discussed, the cleaning operations of operation **220** can result damage the low-k film **302a** of the interconnect structure **300A**, resulting in the increased hydrophilicity and increased k values of the low-k film **302b** of the interconnect structure **300B**. At operation **710**, the low-k film **302b** is subjected to UV treatment via exposure to a UV light source. At operation **510**, the low-k film **302b** of the interconnect structure **300B** is repaired

via exposure to a recovery precursor to form the low-k film **302c** of interconnect structure **300C**. At operation **240**, the interconnect structure **300C** is subjected to a liner deposition process where a liner layer **316** is disposed over the surface of the interconnect structure **300C** including, at least, the low-k film **302c** and/or the surface of the copper layer **310** to form the interconnect structure **300D**. In at least one embodiment, the liner layer **316** of the interconnect structure **300D** is a metal liner deposited by an ALD process over the low-k film **302d**.

(72) In some embodiments, at least one of the low-k films **302a-302d** of one of the interconnect structures **300A-300D** prepared via any of the processes disclosed herein can have a k value of about 2.65 to about 3.0, such as about 2.67 to about 2.8, such as about 2.68 to about 2.76, alternatively about 2.65 to about 2.67, alternatively about 2.67 to about 2.68, alternatively about 2.76 to about 2.8, alternatively about 2.8 to about 3.0. In some embodiments, at least one of the low-k films **302a-302d** of one of the interconnect structures **300A-300D** prepared via any of the processes disclosed herein can have a thickness of about 1200 Å to about 1300 Å, such as about 1225 Å to about 1275 Å, such as about 1240 Å to about 1260 Å, alternatively about 1200 Å to about 1225 Å, alternatively about 1225 Å to about 1240 Å, alternatively about 1260 Å to about 1275 Å, alternatively about 1275 Å to about 1300 Å. In some embodiments, at least one of the low-k films **302a-302c** of one of the interconnect structures **300a-300C** prepared via any of the processes disclosed herein can have a water contact angle of about 65° to about 85°, such as about 70° to about 80°, such as about 75° to about 80°, such as about 77.5° to about 79.5°, alternatively about 65° to about 70°, alternatively about 70° to about 75°, alternatively about 75° to about 77.5°, alternatively about 79.5° to about 80°, alternatively about 80° to about 85°.

(73) Substrate preparation processes and conditions disclosed herein allow for the recovery of low-k values and hydrophobic properties, where such values may have arisen due to various processing procedures and/or variables. Furthermore, such processes provide capability for further liner layer deposition, such as ALD metal film deposition. Interestingly, it has been determined that the order in which such recovery processes are conducted relates to the degree of recovery of such properties and the enablement of ALD metal film deposition.

(74) Additionally, it has been found that the recovery of hydrophobic properties should be intricately balanced with the recovery of low-k values. While full recovery of the low-k values may be desirable, such recovery should be balanced such that the surface hydrophobicity of the repaired substrate is adequate to allow capability for ALD metal film deposition. The processes disclosed herein integrate sequential recovery operations that allow for operational control and provide balanced recovery of low-k values and hydrophilic/hydrophobic properties favorable for subsequent ALD metal film deposition.

EXAMPLES

Example 1

(75) Samples were prepared in accordance to methods described herein, where a sample includes a low-k film on an etch stop layer, a metal barrier between the etch stop layer and a copper layer, a metal barrier between the copper layer and a substrate. Each of the initial samples exhibited a k value of about 2.61 and a water contact angle of about 105.3° prior to processing. Samples were then subjected to a processing operation including etching, ash, wet cleaning operations, or combinations thereof. The samples were then subjected to various recovery processes, such as (1) no recovery, (2) exposure to a recovery precursor, (3) exposure to a UV light source, (4) simultaneous exposure to a recovery precursor and a UV light source, (5) exposure to a recovery precursor subsequently followed by exposure to a UV light source, and (6) exposure to a UV light source subsequently followed by exposure to a recovery precursor. The samples discussed herein are numerically labelled in accordance to the previously recited recovery process in which the sample undergoes. The resulting k values were measured in accordance to ASTM F1392. The thickness of the samples were measured both before and after treatment via ASTM F576. The resulting water contact angles were also measured in accordance to ASTM D5946. The results are

summarized in Table 1. Each of the samples respective k and water contact angles were compared to the corresponding values before prior to processing to determine property recovery as a function of the implemented recovery process.

(76) TABLE-US-00001 TABLE 1 Summary of water contact angle and k recovery values as a function of recovery process

Water	Δ Water	Contact	Contact	Treatment	k	Δk	Angle	Angle	Pre-
processing	2.61	—	105.3°	—	1	2.86	0.25	68.5°	36.8°
	2	2.75	0.14	76.7°	28.6°	3	2.83	0.22	78.0°
	27.3°	4	2.76	0.15	84.2°	21.1°	5	2.76	0.15
	78.3°	27.0°	6	2.68	0.07	79.9°	25.4°	*Δ values are taken as the absolute difference between the pre-processing value and the recovered value.	

(77) TABLE-US-00002 TABLE 2 Summary of low-k film thickness as a function of recovery process

Thickness	Thickness	Pre-	Post-	Δ recovery	recovery	Thickness	Treatment	(Å)	(Å)	(Å)
1	1261	—	—	2	1292	1284	8	3	1290	1235
	55	4	1275	1239	36	5	1262	1217	45	6
	1294	1238	56	*Δ values are taken as the absolute difference between the pre-recovery value and the recovered value.						

(78) As can be determined from analysis of Table 1, recovery treatments where the sample is subjected to some form of exposure to a recovery precursor (e.g., treatments 2 and 4-6) result in increased k value recovery. Furthermore, recovery treatments including exposure to both a recovery precursor and a UV light source (e.g., treatments 4-6) exhibit increases in both water contact angle and k value recovery. Without being bound by theory, such recovery phenomena may be understood by the molecular structures of FIGS. 4A-4C. For instance, the pre-processing sample can be illustrated by FIG. 4A where the low-k film includes Si—O bonds, Si—CH₃ bonds, and Si—H bonds. Sample 1 (e.g., a processed sample not undergoing a recovery process) can be illustrated by FIG. 4B where the low-k film includes a decreased number of Si—CH₃ bonds the formation of Si—OH bonds. The formation of the Si—OH bonds can increase the hydrophilicity and k value of the low k film, as indicated by the increased Δk and Δwater contact angle value relative to Samples 2-6. Samples 2-6 (e.g., processed samples undergoing a recovery process) can be illustrated by FIG. 4C where the low-k film has a decreased number of Si—OH bonds and an increased number of Si—CH₃ bonds relative to Sample 1. As such, the difference in recovery values of Samples 2-6 can be attributed to the relative number of Si—OH and Si—CH₃ bonds as compared to the pre-processed sample.

(79) Additionally, it can be determined from Table 2 that recovery treatments including exposure to UV light source result in decreased film thickness. Without being bound by theory, exposing the low-k films to UV light can cause film shrinkage as a result of the intensity of the light source and/or the length of exposure thereto.

Example 2

(80) FIG. 9 is images showing samples having undergone ALD of tantalum nitride (TaN) subsequent processing and various recovery processes. As can be observed, Samples 1-2 and Samples 5-6 exhibit moderate to good continuity over the surface of each sample, respectively. Without being bound by theory, this finding suggests that the surface hydrophobic/hydrophilic properties of these samples are suitable for ALD of a metal film. In contrast, the pre-processed sample and Sample 4 do not exhibit the same uniformity as Samples 1-2 and Samples 5-6. As previously discussed, hydrophilic/hydrophobic properties of the surface of a sample should be adequate to promote favorable and subsequent ALD metal film deposition. Additionally, surface homogeneity is desired in hydrophilic/hydrophobic properties to enable smooth ALD nucleation.

(81) While the recovery process of Sample 4 promotes substantial recovery of low-k values, it also promotes a large degree of surface hydrophobicity recovery, so much so that subsequent ALD metal film deposition is hindered. As previously discussed, the recovery of hydrophobic properties can be balanced with the recovery of low-k values so to allow for subsequent ALD metal film deposition. Interestingly, Samples 5-6 exhibit good continuity over the surface of each sample upon undergoing ALD of TaN, suggesting that the surface hydrophobic/hydrophilic properties of these samples are suitable for ALD of a metal film. Furthermore, Samples 5-6 exhibit substantial recovery of surface hydrophobic properties and k value, as evidenced in Table 1. Thus, it has been

found that the sequential recovery processes of Sample 5-6 (e.g., (5) exposure to a recovery precursor subsequently followed by exposure to a UV light source and (6) exposure to a UV light source subsequently followed by exposure to a recovery precursor) adequately balance recovery of low-k values and hydrophilic/hydrophobic properties such that the surface of the resulting films are favorable for subsequent ALD metal film deposition.

(82) Overall, the present disclosure provides methods by which to recover properties of damaged low-k films. Processes disclosed herein generally include a processing operation that can damage the molecular structure of the low-k film causing an increase in k value and hydrophilicity. As discussed herein, the sequential recovery processes implemented herein (e.g., exposure to a recovery precursor subsequently followed by exposure to a UV light source or exposure to a UV light source subsequently followed by exposure to a recovery precursor) enable high degrees of property recovery. Additionally, the sequential recovery processes disclosed herein provide a balance between the recovery of low-k values and recovery of hydrophilic/hydrophobic properties such that the surface of the resulting films are favorable for subsequent ALD metal film deposition.

(83) For the purposes of this present disclosure, and unless otherwise specified, the term “alkyl” or “alkyl group” interchangeably refers to a hydrocarbyl group consisting of carbon and hydrogen atoms. An alkyl group can be substituted or unsubstituted and can be linear, branched, or cyclic.

(84) For the purposes of this present disclosure, and unless otherwise specified, the term “cycloalkyl” or “cycloalkyl group” interchangeably refers to a hydrocarbyl group wherein the carbon atoms form one or more ring structures.

(85) For the purposes of this present disclosure, and unless otherwise specified, the term “alkenyl” or “alkenyl group” interchangeably refers to a linear unsaturated hydrocarbyl group comprising a C=C bond therein.

(86) For the purposes of this present disclosure, and unless otherwise specified, the term “aryl” or “aryl group” interchangeably refers to a hydrocarbyl group comprising an aromatic ring structure therein.

(87) While the foregoing is directed to embodiments of the present disclosure, other and further embodiments of the disclosure may be devised without departing from the basic scope thereof, and the scope thereof is determined by the claims that follow.

Claims

1. A method, comprising: positioning a substrate within a processing chamber, the substrate comprising a first low-k film having a first water contact angle, the first low-k film disposed over an interconnect structure; cleaning the substrate within the processing chamber to form a cleaned substrate, the cleaned substrate comprising a damaged low-k film having a second water contact angle and the damaged low-k film is a product of the first low-k film; exposing the cleaned substrate to a recovery precursor to form a recovered substrate, the recovered substrate comprising a recovered low-k film and the recovered low-k film is a product of the damaged low-k film; exposing the recovered substrate to a UV light source to form a treated substrate, the treated substrate comprising a treated low-k film having a third water contact angle and the treated low-k film is a product of the recovered low-k film, wherein each of the first low-k film and the treated low-k film independently comprise a k value and the k value of the first low-k film is less than the k value of the treated low-k film; and depositing a liner layer over the treated substrate via atomic layer deposition (ALD).

2. The method of claim 1, wherein each of the first low-k film and the damaged low-k film independently comprise a k value and the k value of the first low-k film is less than the k value of the damaged low-k film.

3. The method of claim 1, wherein each of the damaged low-k film and the treated low-k film independently comprise a k value and the k value of the damaged low-k film is greater than the k

value of the treated low-k film.

4. The method of claim 1, wherein the first water contact angle is greater than the second water contact angle.

5. The method of claim 1, wherein the second water contact angle is less than the third water contact angle.

6. The method of claim 1, wherein the first water contact angle is greater than the second water contact angle, wherein the second water contact angle is less than the third water contact angle.

7. The method of claim 1, wherein each of the first low-k film, the damaged low-k film, and the treated low-k film independently comprise a k value, wherein: the k value of the first low-k film is less than the k value of the damaged low-k film; and the k value of the damaged low-k film is greater than the k value of the treated low-k film.

8. The method of claim 1, wherein exposing the cleaned substrate to a recovery precursor to form a recovered substrate comprises: introducing the recovery precursor to the processing chamber using a precursor gas flow rate of about 100 milligrams per minute (mgm) to about 2000 mgm; introducing a carrier gas into the processing chamber using a gas flow rate of about 1000 standard cubic centimeters per minute (sccm) to about 5000 sccm; and maintaining a pressure of about 3 Torr to about 100 Torr and a temperature of about 75° C. to about 500° C. within the processing chamber.

9. The method of claim 1, wherein the UV light source comprises an intensity of about 400 W/in to about 800 W/in.

10. The method of claim 1, wherein the liner layer comprises a thickness of about 1200 Å to about 1300 Å.

11. A method, comprising: positioning a substrate within a processing chamber, the substrate comprising a first low-k film having a first water contact angle, the first low-k film disposed over an interconnect structure; cleaning the substrate within the processing chamber to form a cleaned substrate, the cleaned substrate comprising a damaged low-k film having a second water contact angle and the damaged low-k film is a product of the first low-k film; exposing the cleaned substrate to a UV light source to form a treated substrate, the treated substrate comprising a treated low-k film having a third water contact angle and the treated low-k film is a product of the damaged low-k film; exposing the treated substrate to a recovery precursor to form a recovered substrate, the recovered substrate comprising a recovered low-k film and the recovered low-k film is a product of the treated low-k film, wherein each of the first low-k film and the recovered low-k film independently comprise a k value, the k value of the first low-k film being less than the k value of the recovered low-k film; and depositing a liner layer over the recovered substrate via atomic layer deposition (ALD).

12. The method of claim 11, wherein each of the first low-k film and the damaged low-k film independently comprise a k value, the k value of the first low-k film being less than the k value of the damaged film.

13. The method of claim 11, wherein each of the damaged low-k film and the recovered low-k film independently comprise a k value, the k value of the damaged low-k film being greater than the k value of the recovered low-k film.

14. The method of claim 11, wherein the first water contact angle is greater than the second water contact angle.

15. The method of claim 11, wherein the second water contact angle is less than the third water contact angle.

16. The method of claim 11, wherein the first water contact angle is greater than the second water contact angle, and the second water contact angle is less than the third water contact angle.

17. The method of claim 11, wherein each of the first low-k film, the damaged low-k film, and the recovered low-k film independently comprise a k value, wherein: the k value of the first low-k film is less than the k value of the damaged low-k film; and the k value of the damaged low-k film is

greater than the k value of the recovered low-k film.

18. The method of claim 11, wherein the UV light source comprises an intensity of about 400 W/in to about 800 W/in.

19. The method of claim 11, wherein the liner layer comprises a thickness of about 1200 Å to about 1300 Å.

20. A method, comprising: positioning a substrate within a processing chamber, the substrate comprising a first low-k film having a first water contact angle, the first low-k film disposed over an interconnect structure; cleaning the substrate within the processing chamber to form a cleaned substrate, the cleaned substrate comprising a damaged low-k film having a second water contact angle and the damaged low-k film is a product of the first low-k film; exposing the cleaned substrate to a recovery precursor to form a recovered substrate, the recovered substrate comprising a recovered low-k film and the recovered low-k film is a product of the damaged low-k film; exposing the recovered substrate to a UV light source to form a treated substrate, the treated substrate comprising a treated low-k film having a third water contact angle and the treated low-k film is a product of the recovered low-k film, wherein each of the first low-k film and the treated low-k film independently comprise a k value and the k value of the first low-k film is less than the k value of the treated low-k film; and depositing a liner layer over the treated substrate via atomic layer deposition (ALD), wherein the first water contact angle is greater than the second water contact angle, and the second water contact angle is less than the third water contact angle.

21. The method of claim 20, wherein the liner layer comprises a thickness of about 1200 Å to about 1300 Å.
