

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250282931

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Morone; Marika et al.

PHOTOINITIATOR PACKAGE COMPRISING SPECIALISED BISACYLPHOSPHINE OXIDE PHOTOINITIATORS AND OPTICAL BRIGHTENER SENSITIZERS

Abstract

A photoinitiator package comprising one or more bisacylphosphine oxide photoinitiators and one or more optical brightener sensitizers, a photopolymerizable composition comprising the photoinitiator package and suitable polymerizable compounds, a method for polymerizing the photopolymerizable composition and a use of the photoinitiator package in photopolymerization applications.

Inventors:	Morone; Marika (Lipomo, IT), Cremona; Emilio (Venegono Superiore, IT)
Applicant:	IGM GROUP B. V. (Waalwijk, NL)
Family ID:	1000008657159
Appl. No.:	18/862601
Filed (or PCT Filed):	May 05, 2023
PCT No.:	PCT/EP2023/061936

Foreign Application Priority Data

EP	22172087.3	May. 06, 2022
----	------------	---------------

Publication Classification

Int. Cl.: C08K5/5397 (20060101); C08F2/50 (20060101); C08K5/1575 (20060101); C08K5/353 (20060101); C09D7/63 (20180101); C09D11/101 (20140101); C09D11/38 (20140101); C09J11/06 (20060101)

CPC C08K5/5397 (20130101); C08F2/50 (20130101); C08K5/1575 (20130101); C08K5/353 (20130101); C09D7/63 (20180101); C09D11/101 (20130101); C09D11/38 (20130101); C09J11/06 (20130101)

Background/Summary

FIELD OF THE INVENTION

[0001] The present invention relates to a photoinitiator package comprising one or more bisacylphosphine oxide photoinitiators and one or more optical brightener sensitizers, a photopolymerizable composition comprising the photoinitiator package and suitable polymerizable compounds, a method for polymerizing the photopolymerizable composition and a use of the photoinitiator package in photopolymerization applications.

BACKGROUND TO THE INVENTION

[0002] Photoinitiators for promoting the radical polymerisation of ethylenically unsaturated compounds may be classed as either Norrish Type-I, wherein an electronically excited photoinitiator fractures to form a free radical that acts to initiate the radical polymerisation, or Norrish Type-II, wherein an electronically excited photoinitiator abstracts a hydrogen radical from a further molecule to form a free radical from said further molecule, said free radical acting to initiate the radical polymerisation. Whilst Type-II photoinitiators require the presence of certain additives/co-initiators, these additives/co-initiators are not generally required for Type-I photoinitiators.

[0003] The development of new Type-I photoinitiators is a key area of research in the field of resin curing. In addition to the provision of novel Type-I photoinitiators, the provision of Type-I photoinitiator packages, wherein the activity of the Type-I photoinitiator is enhanced by the presence of other compounds, such as photosensitizers. These compounds absorb light at a different wavelength to that of the photoinitiator itself and transfer energy to the photoinitiator, improving the energy absorption by the photoinitiator.

[0004] Phosphine oxides are a well-known family of Type-I photoinitiators that provide excellent activity due to the highly reactive phosphinoyl radical formed upon fragmentation. Whilst excellent photoinitiators in deep-cure systems, they are notoriously much less effective at achieving surface curing. As such, blends of phosphine oxide photoinitiators with other photoinitiators known to be more effective at surface curing are often used to ensure a thorough cure.

[0005] How well different Type-I photoinitiators interact with sensitizers is difficult to predict and often depends on the structure and energy levels of the photoinitiator. The provision of highly active photoinitiator packages is desirable as improved photopolymerization may be achieved without the need to develop new photoinitiators. In particular, an improvement of the surface curing abilities of phosphine oxide photoinitiators would allow these powerful photoinitiators to be more broadly applied.

SUMMARY OF THE INVENTION

[0006] The present observation is based on the observation that combinations of sensitizers and certain bisacylphosphine oxide photoinitiators have unexpectedly excellent photoinitiator properties, including surface curing ability.

[0007] The present invention, in a first aspect, is thus directed to a photoinitiator package comprising: [0008] a) one or more bisacylphosphine oxide photoinitiators, each having a structure according to formula (I):

##STR00001## [0009] wherein each instance of R is independently selected from the group

consisting of C.sub.1-C.sub.4 alkyl; [0010] wherein X is selected from the group consisting of direct single bond, O, S, NR.sup.3, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—; [0011] wherein R.sup.1 is selected from the group consisting of C.sub.1-C.sub.40 alkyl and interrupted C.sub.2-C.sub.40 alkyl being interrupted by one or more O or C.sub.3-C.sub.8 cycloalkylene, wherein said C.sub.1-C.sub.40 alkyl or interrupted C.sub.2-C.sub.40 alkyl may be unsubstituted or substituted by one or more groups selected from OH and R.sup.2; [0012] wherein R.sup.2 is

##STR00002## [0013] wherein R.sup.3 is selected from the group consisting of hydrogen, (CO)R.sup.4, phenyl, C.sub.1-C.sub.12 alkyl, C.sub.2-C.sub.12 alkyl being interrupted by one or more O, wherein said C.sub.1-C.sub.12 alkyl or interrupted C.sub.2-C.sub.12 alkyl is unsubstituted or substituted by one or more C.sub.3-C.sub.7 cycloalkyl, OH or by NCO, C.sub.3-C.sub.12 cycloalkyl which is unsubstituted or substituted by one or more C.sub.1-C.sub.4 alkyl, C.sub.1-C.sub.4 alkoxy, OH or by NCO; and [0014] wherein R.sup.4 is selected from the group consisting of C.sub.1-C.sub.12 alkyl or C.sub.2-C.sub.12 alkyl which is interrupted by one or more O, wherein said C.sub.1-C.sub.12 alkyl or interrupted C.sub.2-C.sub.12 alkyl is unsubstituted or substituted by one or more C.sub.3-C.sub.7-cycloalkyl, OH, NCO or by phenyl which is substituted by NCO; C.sub.3-C.sub.12 cycloalkyl; C.sub.2-C.sub.10 alkenyl which is unsubstituted or substituted by one or more C.sub.1-C.sub.4 alkyl, OH or C.sub.1-C.sub.4 alkoxy; C.sub.6-C.sub.14 aryl which is unsubstituted or substituted by C.sub.1-C.sub.12 alkyl, C.sub.1-C.sub.12 alkoxy, NCO or by NCO-substituted C.sub.1-C.sub.12 alkyl. [0015] b) one or more optical brightener sensitizers.

[0016] In a second aspect, the present invention is directed to a photopolymerizable composition, comprising: [0017] a) one or more ethylenically unsaturated, free-radical polymerizable compounds; [0018] b) the photoinitiator package according to the first aspect.

[0019] In a third aspect, the present invention is directed to a method for photocuring photopolymerizable compositions, coatings, adhesives and inks, said method comprising the following steps in the given order: [0020] a) coating or printing the photopolymerizable composition according to the second aspect onto a substrate, and [0021] b) photopolymerizing said coated or printed composition with a light source on said substrate.

[0022] In a final aspect, the present invention is directed to a use of the photoinitiator package according to the first aspect in the production of printing inks, screen-printing inks, gravure printing inks, solder masks, etch offset-printing inks, flexographic-printing inks, gravure printing inks, ink jet inks, resist material, insulators, encapsulants, image-recording material, solder mask, passivation layer, protective coating, 3D-printing objects and molds, holographic applications, optical fiber coating, waveguide and lens, overprint varnish, wood, vinyl, metal and plastic coatings.

Definitions

[0023] In the present description the expressions “alkyl” or “alkyl group” mean, where not differently indicated, a linear or branched, saturated alkyl chain containing the given number of carbon atoms and includes all possibilities for each number of carbon atoms in the alkyl group, i.e. for three carbon atoms: n-propyl and i-propyl; for four carbon atoms: n-butyl, i-butyl, s-butyl and t-butyl etc.

[0024] The expressions “aryl” or “aryl group” include, for example, a substituted or unsubstituted aryl group, such as a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, an anthracenyl group, an indenyl group, a fluorenyl group.

[0025] The expressions “heteroaryl” or “heteroaryl group” include, for example, a substituted or unsubstituted heteroatom-containing aromatic ring system, such as pyridine, pyrrole, furan, triazine, indole, quinolone, thiophene etc.

[0026] The expression “C.sub.1-C.sub.40 alkyl which is interrupted by one or more oxygens” means that, in case more than one oxygen atom is present, said oxygen atoms are separated from

one another by at least one methylene group, i.e. the oxygen atoms are non-consecutive. Examples include the following: —OCH.sub.2OCH.sub.3, —OCH.sub.2CH.sub.2OCH.sub.2CH.sub.3, —O[CH.sub.2CH.sub.2O].sub.vCH.sub.3, —O[CH.sub.2CH.sub.2O].sub.vOH, —O[CH.sub.2CH.sub.2O].sub.vCH.sub.2CH.sub.3, —CH.sub.2O[CH.sub.2CH.sub.2O].sub.vCH.sub.3 with v=1-19, —O[CH.sub.2CH.sub.2CH.sub.2O].sub.pOH, —O[CH.sub.2CH.sub.2CH.sub.2O].sub.pCH.sub.3, —O[CH.sub.2CH.sub.2CH.sub.2O].sub.pCH.sub.2CH.sub.3, —CH.sub.2O[CH.sub.2CH.sub.2CH.sub.2O].sub.pCH.sub.3 with p=1-12.

[0027] When a group is substituted, the term “substituted” means that said group bears one or more substituents, said substituents being preferably selected from halogen atom, alkyl, cycloalkyl, alkoxy, alkylamino, dialkylamino, alkylthio or arylthio group, heterocyclic groups; more preferably selected from methyl, ethyl, isopropyl, tert-butyl, phenyl, trifluoromethyl, cyano, acetyl, ethoxycarbonyl, carboxyl, carboxylate, amino, methylamino, dimethylamino, ethylamino, diethylamino, isopropylamino, diisopropylamino, cyclohexylamino, dicyclohexylamino, acetylamino, piperidino, pyrrolidyl, methoxy, ethoxy, propoxy, isopropoxy, butoxy, pentyloxy, phenoxy, hydroxyl, acetoxy, —PO.sub.3H, methylthio, ethylthio, i-propylthio, n-propylthio, phenylthio, mercapto, acetylthio, thiocyno, methylsulfinyl, methylsulfonyl, dimethylsulfonyl, sulfonate groups, fluorine atom, chlorine atom, bromine atom, iodine atom, trimethylsilyl, pentamethyldisilyl, triethylsilyl, trimethylstannyl, furyl, thienyl, pyridyl and morpholino.

[0028] The expression “a direct bond” means that a linking group is not present, and a direct bond links the two moieties on either side.

[0029] A methylene group refers to an sp³ hybridised carbon connected to two hydrogen groups, i.e. —CH.sub.2R, whilst a methanetriyl group refers to an sp³ hybridised carbon connected to one hydrogen group, i.e. —CHR.sub.2.

[0030] Photoinitiators may be classed as either Norrish Type-I, wherein an electronically excited photoinitiator fractures to form a free radical that acts to initiate the radical polymerisation, or Norrish Type-II, wherein an electronically excited photoinitiator abstracts a hydrogen radical from a further molecule to form a free radical from said further molecule, said free radical acting to initiate the radical polymerisation, as is well understood by the person skilled in the art.

[0031] The term “photopolymerization package” refers to a combination of one or more photoinitiators with any component that interacts with said photoinitiator to influence the photoinitiator properties of the photopolymerization package, for example synergists and/or sensitizers. Not included in the term “photopolymerization package” are photopolymerizable monomers or any further additives that do not affect the photoinitiator properties of the photopolymerization package, for examples fillers, pigments, antistatic agents, wetting agents or flow enhancers, adhesion enhancers and/or plasticizers that are present in order to modify either the properties of the polymerizable composition (e.g. the flow properties of said polymerizable composition) or the mechanical properties or appearance of the resultant cured composition. Furthermore, the term “photopolymerization package”, in the context of the present invention, means that the components of said package are provided together as a blend, preferably in the form of a blend that is liquid at 25° C. and standard pressure.

[0032] In the context of the present invention, for a blend to be termed “liquid” it must be a monophasic liquid, i.e. blends that are suspensions having a solid and a liquid phase would not be classed as “liquid” in the context of the present invention, as would also be the case for emulsions that have multiple immiscible liquid phases.

Description

DETAILED DESCRIPTION

[0033] Bisacylphosphine Oxide Photoinitiator(s)

[0034] One of the essential features of the photoinitiator package according to the present invention is one or more bisacylphosphine oxide photoinitiators.

[0035] The one or more bisacylphosphine oxide photoinitiators each have a structure according to formula (I)

##STR00003## [0036] wherein each instance of R is independently selected from the group consisting of C.sub.1-C.sub.4 alkyl; [0037] wherein X is selected from the group consisting of direct single bond, O, S, NR.sup.3, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—; [0038] wherein R.sup.1 is selected from the group consisting of C.sub.1-C.sub.40 alkyl and interrupted C.sub.2-C.sub.40 alkyl being interrupted by one or more O or C.sub.3-C.sub.8 cycloalkylene, wherein said C.sub.1-C.sub.40 alkyl or interrupted C.sub.2-C.sub.40 alkyl may be unsubstituted or substituted by one or more groups selected from OH and R.sup.2; [0039] wherein R.sup.2 is

##STR00004## [0040] wherein R.sup.3 is selected from the group consisting of hydrogen, (CO)R.sup.4, phenyl, C.sub.1-C.sub.12 alkyl, C.sub.2-C.sub.12 alkyl being interrupted by one or more O, wherein said C.sub.1-C.sub.12 alkyl or interrupted C.sub.2-C.sub.12 alkyl is unsubstituted or substituted by one or more C.sub.3-C.sub.7 cycloalkyl, OH or by NCO, C.sub.3-C.sub.12 cycloalkyl which is unsubstituted or substituted by one or more C.sub.1-C.sub.4 alkyl, C.sub.1-C.sub.4 alkoxy, OH or by NCO; and [0041] wherein R.sup.4 is selected from the group consisting of C.sub.1-C.sub.12 alkyl or C.sub.2-C.sub.12 alkyl which is interrupted by one or more O, wherein said C.sub.1-C.sub.12 alkyl or interrupted C.sub.2-C.sub.12 alkyl is unsubstituted or substituted by one or more C.sub.3-C.sub.7-cycloalkyl, OH, NCO or by phenyl which is substituted by NCO; C.sub.3-C.sub.12 cycloalkyl; C.sub.2-C.sub.10 alkenyl which is unsubstituted or substituted by one or more C.sub.1-C.sub.4 alkyl, OH or C.sub.1-C.sub.4 alkoxy; C.sub.6-C.sub.14 aryl which is unsubstituted or substituted by C.sub.1-C.sub.12 alkyl, C.sub.1-C.sub.12 alkoxy, NCO or by NCO-substituted C.sub.1-C.sub.12 alkyl.

[0042] Each instance of R may be independently selected from the group consisting of C.sub.1-C.sub.4 alkyl, i.e. from methyl, ethyl, n-propyl, i-propyl, n-butyl, s-butyl, i-butyl and t-butyl. It is particularly preferred that each instance of R is selected from methyl and ethyl. Most preferably each instance of R is methyl.

[0043] X is selected from the group consisting of direct single bond, O, S, NR.sup.3, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—. More preferably, X is selected from the group consisting of direct single bond, O, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—. Yet more preferably, X is selected from the group consisting of direct single bond —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—. Most preferably, X is a direct single bond.

[0044] When X is selected from the group consisting of direct single bond, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—, this has the consequence that the phosphorus atom of the bisacyl phosphine oxide moiety is bonded to carbon, rather than to oxygen, sulfur, or nitrogen. Bisacyl phosphine oxides having phosphorus bonded to carbon, i.e. X is selected from the group consisting of direct single bond, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2— are particularly preferred due to having improved stability and/or improved photoinitiation properties.

[0045] R.sup.1 is selected from the group consisting of C.sub.1-C.sub.40 alkyl and interrupted C.sub.2-C.sub.40 alkyl being interrupted by one or more O or C.sub.3-C.sub.8 cycloalkylene, wherein said C.sub.1-C.sub.40 alkyl or interrupted C.sub.2-C.sub.40 alkyl may be unsubstituted or substituted by one or more groups selected from OH and R.sup.2; [0046] wherein R.sup.2 is

##STR00005##

[0047] In some embodiments no R.sup.2 is present, meaning that the structure according to

Formula (I) has a single bisacylphosphine oxide moiety.

[0048] In such embodiments, it is preferred that R^{sup.1} is selected from the group consisting of C_{sub.1}-C_{sub.20} alkyl,

—(CH_{sub.2}CH_{sub.2}O—)_{sub.n}CH_{sub.3}, and —(CH_{sub.2}CH_{sub.2}O—)_{sub.n}H, wherein n is an integer in the range from 1 to 20.

[0049] It is particularly preferred that R^{sup.1} is C_{sub.1}-C_{sub.20} alkyl.

[0050] Especially preferred are embodiments wherein X is single direct bond and R^{sup.1} is C_{sub.1}-C_{sub.20} alkyl.

[0051] It is particularly preferred in such embodiments that each instance of R is methyl.

[0052] Similarly, embodiments wherein X is O and R^{sup.1} is —(CH_{sub.2}CH_{sub.2}O—)_{sub.n}CH_{sub.3} or —(CH_{sub.2}CH_{sub.2}O—)_{sub.n}H are also especially preferred. It is particularly preferred in such embodiments that each instance of R is methyl.

[0053] In other embodiments, at least one instance of R^{sup.2} is present, meaning that the structure according to Formula (I) has more than one bisacylphosphine oxide moiety.

[0054] Such embodiments are preferably described by Formula (I) wherein R^{sup.1} has a structure according to formula (II):

##STR00006## [0055] wherein each instance of M is independently selected from (CH_{sub.2}CH_{sub.2}O) and (CH_{sub.2}CH(CH_{sub.3})O); [0056] wherein each instance of Y is independently selected from hydrogen and C_{sub.1}-C_{sub.4} alkyl; [0057] wherein each instance of Z has the structure CH_{sub.2}(M^{sup.1})_{sub.c}R^{sup.2}; [0058] wherein each instance of M^{sup.1} is independently selected from (OCH_{sub.2}CH_{sub.2}) and (OCH(CH_{sub.3})CH_{sub.2}) [0059] wherein a is an integer in the range from 0 to 15; [0060] wherein b is an integer in the range from 0 to 6; [0061] wherein each instance of c is independently an integer in the range from 0 to 15; [0062] wherein m is an integer in the range from 0 to 2; and [0063] wherein each instance of X is independently selected from the group consisting of —CH_{sub.2}CO_{sub.2}—, and [0064] —CH_{sub.2}CH_{sub.2}CO_{sub.2}—.

[0065] Such structures are typically formed by combining a central polyol core with multiple BAPO-based carboxylic acid residues, wherein ethylene glycol/propylene glycol spacers (i.e. units M and M^{sup.1}) are optionally used to separate the central polyol core from the BAPO-based carboxylic acid residues.

[0066] Suitable polyol cores include glycerol, wherein b=0, m=1 and Y=H, trimethylolpropane, wherein b=1, m=1 and Y=ethyl, pentaerythritol, wherein b=1, m=0, neopentyl glycol, wherein b=1 m=2 and both instances of Y=methyl, ethylene glycol, wherein b=0, m=2, and both instances of Y=H; 1,6-hexanediol, wherein b=4, m=2 and both instances of Y=H.

[0067] Other suitable polyols include propylene glycol, 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 2,3-butanediol, 1,2-hexanediol, 1,5-hexanediol, 2,5-hexanediol. The skilled person would be aware of which values of b and m as well as choice of Y correspond to these polyols.

[0068] Particularly preferred polyol cores are glycerol, wherein b=0, m=1 and Y=H, trimethylolpropane, wherein b=1, m=1 and Y=ethyl, pentaerythritol, wherein b=1, m=0.

[0069] When a glycerol core is used, R^{sup.1} is termed “optionally ethoxylated/propoxylated glycerol”.

[0070] When a trimethylolpropane core is used, R^{sup.1} is termed “optionally ethoxylated/propoxylated trimethylolpropane”.

[0071] When a pentaerythritol core is used, R^{sup.1} is termed “optionally ethoxylated/propoxylated pentaerythritol”.

[0072] When a neopentyl glycol core is used, R^{sup.1} is termed “optionally ethoxylated/propoxylated neopentyl glycol”.

[0073] When an ethylene glycol core is used, R^{sup.1} is termed “optionally ethoxylated/propoxylated ethylene glycol”.

[0074] When a 1,6-hexanediol core is used, R^{sup.1} is termed “optionally ethoxylated/propoxylated

1,6-hexanediol”.

[0075] It is particularly preferred that a is an integer in the range from 1 to 15 and each instance of c is an integer in the range from 1 to 15, wherein the sum of a and each instance of c is in the range from 3 to 20, more preferably in the range from 3 to 15, most preferably in the range from 3 to 10.

[0076] Such embodiments are termed “ethoxylated/propoxylated polyol”, wherein polyol may be glycerol, trimethylolpropane, pentaerythritol, neopentyl glycol, ethylene glycol or 1,6-hexanediol.

[0077] It is particularly preferred that R.sup.1 is selected from the group consisting of C.sub.1-C.sub.20 alkyl, —(CH.sub.2CH.sub.2O—).sub.nCH.sub.3, and —(CH.sub.2CH.sub.2O—).sub.nH, wherein n is an integer in the range from 1 to 20, ethoxylated/propoxylated glycerol, ethoxylated/propoxylated trimethylolpropane, and ethoxylated/propoxylated pentaerythritol.

[0078] When R.sup.1 is a C.sub.1-C.sub.20 alkyl, it is particularly preferred that R.sup.1 is a C.sub.1-C.sub.15 alkyl, more preferably a C.sub.1-C.sub.12 alkyl.

[0079] Examples of particularly preferred bisacylphosphine oxide photoinitiators having a structure according to formula (I) include:

##STR00007## ##STR00008## ##STR00009## [0080] wherein each instance of a and each instance of c are independently as defined for formula (II).

[0081] It is particularly preferred that each of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I) are liquid at 25° C. and standard pressure.

Optical Brightener Sensitizer(s)

[0082] The other essential feature of the photoinitiator package according to the present invention is the presence of one or more optical brightener sensitizers.

[0083] As would be understood by the person skilled in the art, the term “sensitizer” in “one or more optical brightener sensitizer” explains the purpose of the optical brightener in the photoinitiator package and does not limit the choice of the optical brightener that may be employed.

[0084] Furthermore, the person skilled in the art would be well aware that an optical brightener is a chemical compound that absorbs light in the ultraviolet and violet region of the EM-spectrum and re-emits the light in the blue region via fluorescence. Optical brighteners have been employed in laundry detergents, in paper manufacturing, cosmetics, and textile whitening, as well as in some photopolymerizable compositions for the purpose of improving the optical properties of the cured composition.

[0085] In the broadest sense, any compound known for use as an optical brightener may be used in the photoinitiator package according to the present invention.

[0086] Examples of such well-known optical brighteners include compounds with building blocks including stilbene, triazine, thioazole, benzoxale, coumarin, xanthene, triazole, oxazole, thiophene and pyrazoline.

[0087] Particularly preferred are optical brighteners having coumarin or (benz) oxazole cores.

[0088] In a first particularly preferred embodiment, at least one of the one or more optical brightener sensitizers has a structure according to formula (III):

##STR00010## [0089] wherein R.sup.3a is selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl, C.sub.6-C.sub.14 aryl, and C.sub.6-C.sub.14 heteroaryl, [0090] R.sup.4a is selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl, and OR.sup.1a, and each of R.sup.5a to R.sup.8a is independently selected from the group consisting of hydrogen, halogen, alkyl, OR.sup.1a, and NR.sup.2a.sub.2; [0091] wherein each instance of R.sup.1a is selected from hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, and each instance of R.sup.2a is selected from hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, wherein each instance of R.sup.1a to R.sup.8a may optionally be joined to one or more further instances of R.sup.1a to R.sup.8a to form one or more 5-membered or 6-membered rings.

[0092] In one preferred embodiment, R.sup.3a is selected from the group consisting of hydrogen

and C.sub.1-C.sub.10 alkyl, or R.sup.4a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl.

[0093] In another preferred embodiment, R.sup.3a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl, and R.sup.4a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl.

[0094] In another preferred embodiment, R.sup.7a is selected from the group consisting of OR.sup.1a, and NR.sup.2a.sub.2, most preferably R.sup.7a is NR.sup.2a.sub.2.

[0095] In a particularly preferred embodiment, R.sup.3a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl or R.sup.4a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl, whilst R.sup.7a is selected from the group consisting of OR.sup.1a, and NR.sup.2a.sub.2, most preferably R.sup.7a is NR.sup.2a.sub.2.

[0096] In an especially preferred embodiment, R.sup.3a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl, R.sup.4a is selected from the group consisting of hydrogen and C.sub.1-C.sub.10 alkyl, and R.sup.7a is selected from the group consisting of OR.sup.1a, and NR.sup.2a.sub.2, most preferably R.sup.7a is NR.sup.2a.sub.2.

[0097] At least one of, preferably all of, the coumarin-based sensitizers are selected from the group consisting of coumarin, 7-amino-4-(trifluoromethyl) coumarin, 3-(2-benzothiazolyl)-7-(diethylamino) coumarin, 7-hydroxy-4-(trifluoromethyl) coumarin, 7-(ethylamino)-4,6-dimethylcoumarin, 7-methoxy-4-(trifluoromethyl) coumarin, 7-ethoxy-4-(trifluoromethyl) coumarin, 7-amino-4-methylcoumarin, 7-(diethylamino)-4-methylcoumarin, 3-(2-benzoxazolyl)-7-(diethylamino) coumarin, 7-methylcoumarin, 7-methoxycoumarin, 4-hydroxycoumarin, 5,7-dimethoxycoumarin, 3-(3-biphenyl-4-yl-1,2,3,4-tetrahydro-1-naphthyl)-4-hydroxycoumarin, 6-methylcoumarin, 3-chloro-7-hydroxy-4-methylcoumarin, 7-hydroxycoumarin, 7-hydroxy-6-methoxycoumarin, 7-methoxy-6-hydroxycoumarin, 6-hydroxycoumarin, 7,8-dihydroxy-4-methylcoumarin, 7-Hydroxy-4-methylcoumarin, 7-(dimethylamino)-4-methylcoumarin, 2,3,6,7-Tetrahydro-9-methyl-1H,5H,11H-[1]benzopyrano[6,7,8-ij]quinolizin-11-one, 7-(diethylamino)-4-(trifluoromethyl)-coumarin, and 7-(ethylamino)-4-(trifluoromethyl) coumarin.

[0098] More preferably, at least one of, preferably all of, of the coumarin-based sensitizers are selected from the group consisting of coumarin, 3-(2-benzothiazolyl)-7-(diethylamino) coumarin, 7-methoxy-4-(trifluoromethyl) coumarin, 7-ethoxy-4-(trifluoromethyl) coumarin, 7-(diethylamino)-4-methylcoumarin, 3-(2-benzoxazolyl)-7-(diethylamino) coumarin, 7-methylcoumarin, 7-methoxycoumarin, 5,7-dimethoxycoumarin, 6-methylcoumarin, 7-(dimethylamino)-4-methylcoumarin, 2,3,6,7-Tetrahydro-9-methyl-1H,5H,11H-[1]benzopyrano[6,7,8-ij]quinolizin-11-one, 7-(diethylamino)-4-(trifluoromethyl)-coumarin, and 7-(ethylamino)-4-(trifluoromethyl) coumarin.

[0099] Most preferably, at least one of, preferably all of, of the coumarin-based sensitizers are selected from the group consisting of coumarin, 7-(diethylamino)-4-methylcoumarin, 7-methylcoumarin, 7-methoxycoumarin, 5,7-dimethoxycoumarin, and 7-(diethylamino)-4-(trifluoromethyl)-coumarin.

[0100] In a second particularly preferred embodiment, at least one of the one or more optical brightener sensitizers has a structure according to formula (IV):

##STR00011## [0101] wherein each of R.sup.1b to R.sup.4b is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, wherein R.sup.1b and R.sup.2b may be joined to form a 6-membered saturated or unsaturated ring, which may be substituted by one or more substituents selected from the group consisting of hydrogen C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl and wherein R.sup.3b and R.sup.4b may be joined to form a 6-membered saturated or unsaturated ring, which may be substituted by one or more substituents selected from the group consisting of hydrogen C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl; and [0102] wherein A represents a linking group represented by any of the following formulas (V) to (IX):

##STR00012## [0103] wherein each * represents a bonding position of A in each formula.

[0104] Each of R.sup.1b to R.sup.4b is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, wherein R.sup.1b and R.sup.2b may be joined to form a 6-membered saturated or unsaturated ring, which may be substituted by one or more substituents selected from the group consisting of hydrogen C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl and wherein R.sup.3b and R.sup.4b may be joined to form a 6-membered saturated or unsaturated ring, which may be substituted by one or more substituents selected from the group consisting of hydrogen C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl.

[0105] In one embodiment, each of R.sup.1b to R.sup.4b is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.6 alkyl and C.sub.6-C.sub.10 aryl.

[0106] In a particularly preferred embodiment, both R.sup.1b and R.sup.3b are joined to R.sup.2b and R.sup.4b, respectively, to form 6-membered saturated or unsaturated rings, which may be substituted by one or more substituents selected from the group consisting of hydrogen C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl.

[0107] In one embodiment of said particularly preferred embodiment, each 6-membered ring formed is aromatic, meaning that at least one of the one or more oxazole-based sensitizers is a benzoxazole-based sensitizer, having a structure according to formula (X):

##STR00013## [0108] wherein each of R.sup.1c to R.sup.8c is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl.

[0109] Preferably each of R.sup.1c to R.sup.8c is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.6 alkyl and C.sub.6-C.sub.10 aryl.

[0110] In one embodiment, each of the one or more oxazole-based sensitizers has a structure according to formula (X).

[0111] In other embodiments, at least one of the one or more oxazole-based sensitizers has a structure according to formula (X), whilst any remaining oxazole-based sensitizers in the photoinitiator package have other structures according to formula (IV).

[0112] Particularly preferred compounds according to Formula (IV) include 2,5-thiophenediylbis(5-tert-butyl-1,3-benzoxazole), 2,2'-(vinylene-di-p-phenylene)bisbenzoxazole, 2,2'-(naphthalene-1,4-diyl)bis(benzoxazole), 2-[4-[2-[4-(benzoxazol-2-yl)phenyl]vinyl]phenyl]-5-methylbenzoxazole, 2,2'-(1,4-phenylene)bis[5-phenyl-oxazole].

Photoinitiator Package

[0113] The photoinitiator package according to the present invention comprises one or more bisacylphosphine oxide photoinitiators as described above and one or more optical brightener sensitizers as described above.

[0114] It is preferred that the photoinitiator package comprises: [0115] a) an amount in the range from 15 to 99.9 wt.-%, more preferably in the range from 30 to 99.0 wt.-%, most preferably in the range from 50 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and

[0116] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 40 wt.-%, most preferably in the range from 3.0 to 35 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0117] In one embodiment, the photoinitiator package comprises: [0118] a) an amount in the range from 15 to 99.9 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0119] b) an amount in the range from 0.1 to 50 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0120] In a further embodiment, the photoinitiator package comprises: [0121] a) an amount in the range in the range from 30 to 99.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0122] b) an amount in the range from 1.0 to 40 wt.-%, relative to the total weight of the

photoinitiator package, of the one or more optical brightener sensitizers.

[0123] In yet a further embodiment, the photoinitiator package comprises: [0124] a) an amount in the range from 50 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0125] b) an amount in the range from 3.0 to 35 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0126] It is further preferred that the photoinitiator package comprises: [0127] a) an amount in the range from 40 to 99.9 wt.-%, more preferably in the range from 60 to 99.0 wt.-%, most preferably in the range from 65 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0128] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 40 wt.-%, most preferably in the range from 3.0 to 35 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0129] In one embodiment, the photoinitiator package comprises: [0130] a) an amount in the range from 40 to 99.9 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0131] b) an amount in the range from 0.1 to 50 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0132] In a further embodiment, the photoinitiator package comprises: [0133] a) an amount in the range in the range from 60 to 99.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0134] b) an amount in the range from 1.0 to 40 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0135] In yet a further embodiment, the photoinitiator package comprises: [0136] a) an amount in the range from 65 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0137] b) an amount in the range from 3.0 to 35 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0138] In addition to the one or more bisacylphosphine oxide photoinitiators and the one or more optical brightener sensitizers, the photoinitiator package may also comprise one or more amines.

[0139] In the broadest sense, the one or more amines according to the present invention may be any amine, including aliphatic, cycloaliphatic, aromatic, aryl aliphatic, heterocyclic, oligomeric or polymeric amines. They may be primary, secondary or tertiary amines, for example, butyl amine, dibutylamine, tributylamine, cyclohexyl amine, benzyldimethyl amine, dicyclohexyl amine, N-phenyl glycine, triethyl amine, phenyl-diethanol amine, triethanolamine, piperidine, piperazine, morpholine, quinolone, esters of dimethylamino benzoic acid, and corresponding derivatives. Furthermore, amine-modified acrylates can be used. Examples of such amine-modified acrylates include acrylates modified by reaction with a primary or secondary amine that are 15 described in U.S. Pat. No. 3,844,916, EP 280222, U.S. Pat. No. 5,482,649 or U.S. Pat. No. 5,734,002.

[0140] Multifunctional amine and polymeric amine derivatives are also suitable for use are Omnipol ASA from IGM Resins B.V., Genopol AB-2 from Rahn A.G., Speedcure 7040 from Lambson Limited or those described in US2013/0012611.

[0141] It would be understood by the person skilled the art that the term “amine” does not include amides or imides, irrespective of whether the nitrogen of the amide/imide is bonded to an alkyl group. Likewise, ammonium salts would not be amines.

[0142] It is preferred that the one or more amines are not Type-I or Type-II photoinitiators, such as well-known aminoketone Type-I initiators. It is further preferred that the one or more amines are not optical brighteners, i.e. compounds that absorb light in the ultraviolet and violet region of the EM-spectrum and re-emits the light in the blue region via fluorescence. As such, it is clear that the only role of the amine in the photopolymerization package is to act as a synergist, improving the

effect of the one or more one or more one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I) and/or the one or more optical brightener sensitizers.

[0143] It is preferred that the one or more amines have a so-called alpha-hydrogen, i.e. a hydrogen bonded to a carbon that is directly bonded to the nitrogen of the amine. It is particularly preferred that this hydrogen is bonded to an sp³-hybridized carbon. As such, it is preferred that the amine has a nitrogen atom having a direct single bond to either a methyl group (i.e. CH₃), a methylene group (i.e. the CH₂ of a CH₂R) or a methanetriyl group (i.e. the CH of a CHR₂).

[0144] Without wishing to be bound by theory, it is believed that the alpha-hydrogen may be easily abstracted by radicals, forming a stabilized alpha-amino-radical, which can play a role in improving the rate of curing, in particular by scavenging molecular oxygen, which may retard the polymerization reaction.

[0145] It is particularly preferred that the nitrogen atom is bonded to at least one alkyl group. It is further preferred that the nitrogen atom is bonded to at least two alkyl groups.

[0146] In one particularly preferred embodiment, the one or more amines are independently selected from the group consisting of amines having the formula NR^AR^BR^C, wherein R^A and R^B are independently selected from optionally substituted alkyl groups and R^C is selected from the group consisting of optionally substituted alkyl groups and optionally substituted aryl groups.

[0147] In said embodiment, the term “optionally substituted aryl groups” does not include aryl groups that have two or more substituents that are linked to form a fused ring system, such as a quinoline, an indole, or a coumarin. Likewise, the term “optionally substituted alkyl groups” does not include substitution that would result in the group no longer being considered as an alkyl group, such as acyl groups (i.e. =O substitution at the first carbon atom of the alkyl chain).

[0148] If present, the one or more amines is preferably present in an amount in the range from 1.0 to 45 wt.-%, more preferably in the range from 3.0 to 35 wt.-%, most preferably in the range from 5.0 to 30 wt.-%, relative to the total weight of the photoinitiator package.

[0149] As such, in one embodiment the photoinitiator package comprises, more preferably consists of: [0150] a) an amount in the range from 15 to 98.9 wt.-%, more preferably in the range from 30 to 96.0 wt.-%, most preferably in the range from 50 to 92.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0151] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 37 wt.-%, most preferably in the range from 3.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; and [0152] c) an amount in the range from 1.0 to 45 wt.-%, more preferably in the range from 3.0 to 35 wt.-%, most preferably in the range from 5.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of one or more amines.

[0153] In a further embodiment, the photoinitiator package comprises, more preferably consists of:

[0154] a) an amount in the range from 15 to 98.9 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0155] b) an amount in the range from 0.1 to 50 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; and [0156] c) an amount in the range from 1.0 to 45 wt.-%, relative to the total weight of the photoinitiator package, of one or more amines.

[0157] In another embodiment, the photoinitiator package comprises, more preferably consists of:

[0158] a) an amount in the range from 30 to 96.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0159] b) an amount in the range from 1.0 to 37 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; and [0160] c) an amount in the range from 3.0 to 35 wt.-%, relative to the total weight of the

photoinitiator package, of one or more amines.

[0161] In yet a further embodiment, the photoinitiator package comprises, more preferably consists of: [0162] a) an amount in the range from 50 to 92.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0163] b) an amount in the range from 3.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; and [0164] c) an amount in the range from 5.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of one or more amines.

[0165] When no amine is present, the photoinitiator package preferably comprises, more preferably consists of: [0166] a) an amount in the range from 50 to 99.9 wt.-%, more preferably in the range from 70 to 99.0 wt.-%, most preferably in the range from 80 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0167] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 30 wt.-%, most preferably in the range from 3.0 to 20 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0168] In another embodiment, the photoinitiator package comprises, more preferably consists of:

[0169] a) an amount in the range from 50 to 99.9 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0170] b) an amount in the range from 0.1 to 50 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0171] In a further embodiment, the photoinitiator package comprises, more preferably consists of:

[0172] a) an amount in the range from 70 to 99.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0173] b) an amount in the range from 1.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0174] In a final embodiment, the photoinitiator package comprises, more preferably consists of:

[0175] a) an amount in the range from 80 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); and [0176] b) an amount in the range from 3.0 to 20 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers.

[0177] If further components other than the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I), the one or more optical brightener sensitizers and the one or more amines are present, then they are preferably further Type-I or Type-II photoinitiators.

[0178] As such, it is preferred that the photoinitiator package comprises, more preferably consists of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I), the one or more optical brightener sensitizers, optionally one or more amines, and optionally one or more further Type-I or Type-II photoinitiators.

[0179] As would be understood by the person skilled in the art, the term “further Type-I or Type-II photoinitiators” means that these further photoinitiators have structures other than the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I).

[0180] Thus, the photoinitiator package preferably consists of: [0181] a) an amount in the range from 15 to 98.9 wt.-%, more preferably in the range from 30 to 96.0 wt.-%, most preferably in the range from 50 to 92.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0182] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 37 wt.-%, most preferably in the range from 3.0 to 30 wt.-%, relative to the total weight of the photoinitiator

package, of the one or more optical brightener sensitizers; [0183] c) optionally, an amount in the range from 1.0 to 45 wt.-%, more preferably in the range from 3.0 to 35 wt.-%, most preferably in the range from 5.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of one or more amines; and [0184] d) optionally, an amount in the range from 0.0 to 84.9 wt.-%, more preferably in the range from 0.0 to 69.0 wt.-%, most preferably in the range from 0.0 to 47.0 wt.-% of further Type-I or Type-II photoinitiators.

[0185] If one or more amines are present, then the photoinitiator package preferably consists of:

[0186] a) an amount in the range from 15 to 98.9 wt.-%, more preferably in the range from 30 to 96.0 wt.-%, most preferably in the range from 50 to 92.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0187] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 37 wt.-%, most preferably in the range from 3.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; [0188] c) an amount in the range from 1.0 to 45 wt.-%, more preferably in the range from 3.0 to 35 wt.-%, most preferably in the range from 5.0 to 30 wt.-%, relative to the total weight of the photoinitiator package, of one or more amines; and [0189] d) optionally, an amount in the range from 0.0 to 83.9 wt.-%, more preferably in the range from 0.0 to 66.0 wt.-%, most preferably in the range from 0.0 to 42.0 wt.-% of further Type-I or Type-II photoinitiators.

[0190] If no amines are present, then the photoinitiator package preferably consists of: [0191] a) an amount in the range from 15 to 99.9 wt.-%, more preferably in the range from 30 to 99.0 wt.-%, most preferably in the range from 50 to 97.0 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); [0192] b) an amount in the range from 0.1 to 50 wt.-%, more preferably in the range from 1.0 to 30 wt.-%, most preferably in the range from 3.0 to 20 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; and [0193] c) optionally, an amount in the range from 0.0 to 84.9 wt.-%, more preferably in the range from 0.0 to 69.0 wt.-%, most preferably in the range from 0.0 to 47.0 wt.-% of further Type-I or Type-II photoinitiators.

[0194] Furthermore, it is preferred that the photoinitiator package is present in the form of a blend that is liquid at 25° C. and standard pressure.

[0195] This means that the one or more bisacylphosphine oxides, the one or more optical brightener sensitizers and the optional one or more amines must be miscible and form a stable liquid blend at the indicated temperature and pressure, rather than being present as a mixture of dry powders or as a suspension or emulsion, for example.

Photopolymerizable Composition

[0196] In a second aspect, the present invention is also directed to a photopolymerizable composition.

[0197] In the broadest sense, the photopolymerizable composition comprises or consist of: [0198]

a) one or more ethylenically unsaturated, free-radical polymerizable compounds; [0199] b) the photoinitiator package according to the first aspect.

[0200] It is preferred that the photopolymerizable composition comprises or consists of: [0201] a)

an amount in the range from 30 to 99.0 wt.-%, more preferably in the range from 50 to 95.0 wt.-%, most preferably in the range from 70 to 90 wt.-%, relative to the total weight of the photopolymerizable composition, of the one or more ethylenically unsaturated, free-radical polymerizable compounds; [0202] b) an amount in the range from 0.5 to 50 wt.-%, more preferably in the range from 0.8 to 40 wt.-%, most preferably in the range from 1.0 to 30 wt.-%, relative to the total weight of the photopolymerizable composition, of the photoinitiator package according to the first aspect.

[0203] In addition to the one or more ethylenically unsaturated, free-radical polymerizable compounds and photoinitiator package according to the first aspect, the photopolymerizable

composition may comprise further components, as would be well-understood by the person skilled in the art.

[0204] Suitable further components include photosensitizers, further photoinitiators, pigments, binders, and conventional additives.

[0205] As such, the photopolymerizable composition comprises, more preferably consists of:

[0206] a) an amount in the range from 30 to 99.0 wt.-%, more preferably in the range from 50 to 95.0 wt.-%, most preferably in the range from 70 to 90 wt.-%, relative to the total weight of the photopolymerizable composition, of the one or more ethylenically unsaturated, free-radical polymerizable compounds; [0207] b) an amount in the range from 0.5 to 50 wt.-%, more preferably in the range from 0.8 to 40 wt.-%, most preferably in the range from 1.0 to 30 wt.-%, relative to the total weight of the photopolymerizable composition, of the photoinitiator package according to the first aspect; [0208] c) optionally, an amount in the range from 0.5 to 30 wt.-%, more preferably in the range from 0.8 to 20 wt.-%, most preferably in the range from 1.0 to 15 wt.-% of one or more further photoinitiators, one or more photosensitizers and/or one or more co-initiators; [0209] d) optionally, an amount in the range from 0.1 to 30 wt.-%, more preferably in the range from 1.0 to 25 wt.-%, most preferably in the range from 10 to 20 wt.-%, relative to the total weight of the photopolymerizable composition, of one or more pigments; [0210] e) optionally, an amount in the range from 5.0 to 60 wt.-%, more preferably in the range from 8.0 to 50 wt.-%, most preferably in the range from 10 to 40 wt.-%, relative to the total weight of the photopolymerizable composition, of one or more binders; and [0211] f) optionally, an amount in the range from 0.01 to 10 wt.-%, more preferably in the range from 0.01 to 8.0 wt.-%, most preferably in the range from 0.01 to 5.0 wt.-%, relative to the total weight of the photopolymerizable composition, of one or more additives.

[0212] In addition, the photopolymerizable composition may be formulated in compositions further comprising water and/or solvents, such as organic solvents.

[0213] It is preferred that no further photoinitiators, photosensitizers or co-initiators are present, beyond those forming part of the photoinitiator package. In other words, all components that contribute to the photopolymerization properties of the photoinitiator are preferably subsumed within the photoinitiator package, as defined above and below.

[0214] The choice of the one or more ethylenically unsaturated, free-radical polymerizable compounds is not particularly limited. Said compounds can contain one or more olefinic double bonds. They can be low-molecular weight (monomeric) or high-molecular weight (oligomeric) compounds.

[0215] Examples of suitable low molecular weight polymerizable compounds (monomeric compounds) having one double bond are alkyl or hydroxyalkyl acrylates or methacrylates, such as methyl-, ethyl-, butyl-, 2-ethylhexyl-, 2-hydroxyethyl- or isobornyl-acrylate; and methyl or ethyl methacrylate. Further examples are resins modified with silicon or fluorine, e.g. silicone acrylates. Further examples of these polymerizable compounds are acrylonitrile, acrylamide, methacrylamide, N-substituted (meth)acrylamides, styrene, alkylstyrenes and halogeno styrenes, vinyl esters such as vinyl acetate, vinyl ethers such as iso-butyl vinyl ether, N-vinylpyrrolidone, vinyl chloride or vinylidene chloride.

[0216] Examples of polymerizable compounds having more than one double bond are the ethylene glycol diacrylate, propylene glycol diacrylate, neopentyl glycol diacrylate, hexamethylene glycol diacrylate, bisphenol A diacrylate, 4,4'-bis-(2-acryloyloxyethoxy)-diphenylpropane, trimethylolpropane triacrylate, pentaerythritol triacrylate or tetraacrylate, vinyl acrylate, divinyl benzene, divinyl succinate, diallyl phthalate, triallyl phosphate, triallyl isocyanurate or tris-(2-acryloylethyl) isocyanurate.

[0217] Examples of high-molecular weight (oligomeric) polyunsaturated compounds are acrylated epoxy resins, acrylated or vinyl-ether- or epoxy-group-containing polyesters, acrylated polyurethanes or acrylated polyethers.

[0218] Further examples of unsaturated oligomers are unsaturated polyester resins which are

usually prepared from maleic acid, phthalic acid and one or more diols and which have molecular weights of from about 500 Da to 3,000 Da. Such unsaturated oligomers can also be referred to as prepolymers.

[0219] Examples of polymerizable compounds which are particularly suitable for the implementation of the present invention, are esters of ethylenically unsaturated carboxylic acids and polyols or polyepoxides, and polymers containing ethylenically unsaturated groups in the chain or in side groups, e.g. unsaturated polyesters, polyamides and polyurethanes and copolymers thereof, alkyl resins, polybutadiene and butadiene copolymers, polyisoprene and isoprene copolymers, polymers and copolymers having (meth)acrylic groups in side chains, as well as mixtures thereof.

[0220] Illustrative examples of unsaturated carboxylic acids or anhydrides, useful for the preparation of the above esters, are acrylic acid, methacrylic acid, maleic anhydride, crotonic acid, itaconic acid, cinnamic acid and unsaturated fatty acids such as linolenic acid and oleic acid. Acrylic and methacrylic acid are preferred.

[0221] Examples of polyols, which can also be esterified, are aromatic and aliphatic and cycloaliphatic polyols, preferably aliphatic and cycloaliphatic polyols. Aromatic polyols are, for example, hydroquinone, 4,4'-dihydroxydiphenyl, 2,2-di(4-hydroxyphenyl) propane, as well as novolaks and resoles.

[0222] Polyepoxides, which can be esterified, include those based on the said polyols, especially the reaction products between aromatic polyols and epichlorohydrin. Also suitable as polyols are polymers and copolymers that contain hydroxyl groups in the polymer chain or in side groups, for example polyvinyl alcohol and copolymers thereof or polymethacrylic acid hydroxyalkyl esters or copolymers thereof. Further suitable polyols are oligoesters carrying hydroxyl terminal groups.

[0223] Examples of aliphatic and cycloaliphatic polyols include alkylene diols containing preferably from 2 to 12 carbon atoms, such as ethylene glycol, 1,2- or 1,3-propanediol, 1,2-, 1,3- or 1,4-butanediol, pentanediol, hexanediol, octanediol, dodecanediol, diethylene glycol, triethylene glycol, polyethylene glycols having molecular weights of preferably from 200 Da to 1,500 Da, 1,3-cyclopentanediol, 1,2-, 1,3- or 1,4-cyclohexanediol, 1,4-dihydroxymethyl cyclohexane, glycerol, tris(β -hydroxy-ethyl)amine, trimethylolethane, trimethylolpropane, pentaerythritol, dipentaerythritol and sorbitol.

[0224] Further suitable ethylenically unsaturated compounds are unsaturated polyamides obtained from unsaturated carboxylic acids and aromatic, aliphatic and cycloaliphatic polyamines having preferably from 2 to 6, preferably from 2 to 4, amino groups. Examples of such polyamines are: ethylenediamine, 1,2- or 1,3-propylenediamine, 1,2-, 1,3- or 1,4-butylenediamine, 1,5-pentylenediamine, 1,6-hexylenediamine, octylenediamine, dodecylene diamine, 1,4-diaminocyclohexane, isophoronediamine, phenylene diamine, bisphenylenediamine, di-(β -aminoethyl) ether, diethylene triamine, triethylenetetramine and di(β -aminoethoxy)- and di(β -aminopropoxy) ethane. Other suitable polyamines are polymers and copolymers which may contain additional amino groups in the side chain and oligoamides containing amino end groups.

[0225] Specific examples of such unsaturated polyamides are methylenebisacrylamide, 1,6-hexamethylene bisacrylamide, diethylenetriamine trismethacrylamide, bis(methacrylamidopropoxy) ethane and N-[(β -hydroxyethoxy)ethyl]-acrylamide.

[0226] Unsaturated polyurethanes are also suitable for the implementation of the present invention as polymerizable compounds, for example those derived from saturated or unsaturated diisocyanates and unsaturated or saturated diols.

[0227] Polybutadiene and polyisoprene and copolymers thereof may also be used.

[0228] Suitable polymerizable compounds include, for example, olefins, such as ethylene, propene, butene and hexene, (meth)acrylates, acrylonitrile, styrene and vinyl chloride. Polymers having unsaturated (meth)acrylate groups in the side chain can also be used as the one or more ethylenically unsaturated, free-radical polymerizable compounds. They may typically be reaction

products of epoxy resins based on novolac with (meth)acrylic acid; homo- or copolymers of vinyl alcohol or hydroxyalkyl derivatives thereof that have been esterified with (meth)acrylic acid; and homo- and co-polymers of (meth)acrylates that have been esterified with hydroxyalkyl (meth)acrylates.

[0229] Examples of photosensitizers are those commonly used in the art, aromatic carbonyl compounds, e.g. benzophenones, thioxanthenes, anthraquinones, and 3-acylcoumarin derivatives, terphenyls, styryl ketones, and 3-(aroylmethylene)-thiazolines, camphorquinones and also eosin, rhodamine and erythrosine dyes.

[0230] Examples of thioxanthenes are thioxanthone, 2-isopropyl thioxanthone, 2-chloro thioxanthone, 2-dodecyl thioxanthone, 2,4-diethyl thioxanthone, 2,4-dimethyl thioxanthone, 1-methoxycarbonyl thioxanthone, 2-ethoxycarbonyl thioxanthone, 3-(2-methoxyethoxycarbonyl)thioxanthone, 4-butoxycarbonyl thioxanthone, 3-butoxycarbonyl-7-methyl thioxanthone, 1-cyano-3-chloro thioxanthone, 1-ethoxycarbonyl-3-chloro thioxanthone, 1-ethoxycarbonyl-3-ethoxy thioxanthone, 1-ethoxycarbonyl-3-amino thioxanthone, 1-ethoxycarbonyl-3-phenylsulfuryl thioxanthone, 3,4-di[2-(2-methoxyethoxy)ethoxycarbonyl]thioxanthone, 1-ethoxycarbonyl-3-(1-methyl-1-morpholinoethyl)thioxanthone, 2-methyl-6-dimethoxymethyl thioxanthone, 2-methyl-6-(1,1-dimethoxybenzyl)thioxanthone, 2-morpholinomethyl thioxanthone, 2-methyl-6-morpholinomethyl thioxanthone, N-allylthioxanthone-3,4-dicarboximide, N-octylthioxanthone-3,4-dicarboximide, N-(1,1,3,3-tetramethylbutyl)-thioxanthone-3,4-dicarboximide, 1-phenoxy thioxanthone, 6-ethoxycarbonyl-1-2-methoxythioxanthone, 6-ethoxycarbonyl-2-methylthioxanthone, thioxanthone-2-polyethylene glycol ester, 2-hydroxy-3-(3,4-dimethyl-9-oxo-9H-thioxanthen-2-yloxy)-N,N,N-trimethyl-1-propanaminium chloride, or those described in the patent application PCT/EP2011/069514, such as n-dodecyl-7-methyl-thioxanthone-3-carboxylate and N,N-disobutyl-7-methyl-thioxanthone-3-carbamide. Also suitable are polymeric thioxanthone derivatives (e.g. Omnipol® TX from IGM Resins B.V., Genopol® TX-1 from Rahn A.G., Speedcure® 7010 from Lambson Limited).

[0231] Example of benzophenones are benzophenone, 4-phenyl benzophenone, 4-methoxy benzophenone, 4,4'-dimethoxybenzophenone, 4,4'-dimethyl benzophenone, 4,4'-dichloro benzophenone, 4,4'-dimethylamino benzophenone, 4,4'-diethylamino benzophenone, 4-methyl benzophenone, 2,4,6-trimethyl benzophenone, 4-(4-methylthiophenyl)benzophenone, 3,3'-dimethyl-4-methoxy benzophenone, methyl 2-benzoyl benzoate, 4-(2-hydroxyethylthio)benzophenone, 4-(4-tolylthio)benzophenone, 4-benzoyl-N,N,N-trimethylbenzene methanaminium chloride, 2-hydroxy-3-(4-benzoylphenoxy)-N,N,N-trimethyl-1-propanaminium chloride monohydrate, 4-(13-acryloyl-1,4,7,10,13-pentaoxatridecyl)benzophenone, 4-benzoyl-N,N-dimethyl-N-[2-(1-oxo-2-propenyl)oxy]ethyl-benzene methanaminium chloride, or those described in U.S. Pat. No. 9,938,231 (e.g. Omnirad® 991 from IGM Resins B.V.).

[0232] Also suitable are polymeric benzophenone derivatives (e.g. Omnipol® BP, Omnipol® 2702 and Omnipol® 682 all from IGM Resins B.V., Genopol® BP-2 from Rahn A.G. and Speedcure® 7005 from Lambson Limited).

[0233] Examples of 3-acylcoumarin derivatives are 3-benzoyl coumarin, 3-benzoyl-7-methoxy coumarin, 3-benzoyl-5,7-di(propoxy) coumarin, 3-benzoyl-6,8-dichloro coumarin, 3-benzoyl-6-chloro coumarin, 3,3'-carbonyl-bis[5,7-di(propoxy) coumarin], 3,3'-carbonyl-bis(7-methoxy coumarin), 3,3'-carbonyl-bis(7-diethylamino coumarin), 3-isobutyroyl coumarin, 3-benzoyl-5,7-dimethoxy coumarin, 3-benzoyl-5,7-diethoxy coumarin, 3-benzoyl-5,7-dibutoxy coumarin, 3-benzoyl-5,7-di(methoxyethoxy) coumarin, 3-benzoyl-5,7-di(allyloxy) coumarin, 3-benzoyl-7-dimethylamino coumarin, 3-benzoyl-7-diethylamino coumarin, 3-isobutyroyl-1,7-dimethylamino coumarin, 5,7-dimethoxy-3-(1-naphthoyl) coumarin, 5,7-dimethoxy-3 (1-naphthoyl)-coumarin, 3-benzoylbenzo[f]coumarin, 7-diethylamino-3-thienoyl coumarin, 3-(4-cyanobenzoyl)-5,7-dimethoxy coumarin, or those described in EP2909243 and WO2017216699.

[0234] Examples of 3-(aroylmethylene) thiazolines are 3-methy-1,2-benzoylmethylene- β -naphtho

thiazoline, 3-methyl-2-benzoylmethylene-benzo thiazoline, 3-ethyl-2-propionylmethylene- β -naphtho thiazoline.

[0235] Examples of other aromatic carbonyl compounds are acetophenone, 3-methoxyacetophenone, 4-phenylacetophenone, benzil, such as that described in WO 2013/164394, 2-acetylnaphthalene, 2-naphthaldehyde, 9,10-anthraquinone, 9-fluorenone, dibenzosuberone, xanthone, 2,5-bis(4-diethylaminobenzylidene)cyclopentanone, α -(para-dimethylamino benzylidene), ketones, such as 2-(4-dimethylamino-benzylidene)-indan-1-one or 3-(4-dimethylaminophenyl)-1-indan-5-yl-propenone, 3-phenylthiophthalimide, N-methyl-3,5-di(ethylthio) phthalimide.

[0236] Particularly preferred are thioxanthenes, and 3-acylcoumarins.

[0237] It was observed that the above photosensitizers increase the activity of the one or more bisacylphosphine oxide photoinitiators without shortening the shelf life of the compositions. Moreover, such compositions have the special advantage that an appropriate choice of the photosensitizer allows the spectral sensitivity of the photoinitiator package to be shifted to any desired wavelength region. The person skilled in the art is able to select the suitable photosensitizer to make the photoinitiator package work at any desired wavelength region.

[0238] Examples of other suitable photoinitiators are camphorquinone, benzophenone, benzophenone derivatives, acetophenone, acetophenone derivatives, dialkoxyacetophenones, α -hydroxyketones, α -aminoketones, 4-aryl-1,3-dioxolanes, benzoin alkyl ethers and benzil ketals, e.g. benzil dimethyl ketal, ketosulfones, e.g. 1-[4-[(4-benzoyl-phenyl)-thio]-phenyl]-2-methyl-2-[(4-methyl-phenyl)-sulfonyl]-propan-1-one (Esacure® 1001, from IGM Resins B.V.), 3-ketocoumarins, for example as described in EP2909243 and WO2017216699, phenylglyoxylates and derivatives thereof, dimeric phenyl glyoxylates, peresters, e.g. benzophenonetetracarboxylic acid peresters, for example as described in EP 126 541, acylphosphine photoinitiators (which can be chosen among mono-acylphosphine oxides, bis-acylphosphine oxides, tris-acylphosphine oxides and multifunctional mono- or bisacylphosphine oxides), halomethyltriazines, hexaaryl bisimidazole/coinitiator systems, e.g. ortho-chlorohexaphenylbisimidazole in combination with 2-mercaptobenzothiazole, ferrocenium compounds or titanocenes, for example dicyclopentadienyl-bis(2,6-difluoro-3-pyrrolo-phenyl) titanium, O-acyloxime ester photoinitiators.

[0239] Examples of α -hydroxyketones and α -aminoketones are 1-hydroxy cyclohexylphenyl ketone, 2-hydroxy-2-methyl-1-phenyl-propane-1-one, 1-[4-(2-hydroxyethoxy)phenyl]-2-hydroxy-2-methyl-1-propane-1-one, 2-hydroxy-1-{4-[4-(2-hydroxy-2-methyl-propionyl)-benzyl]phenyl}-2-ethyl-propane-1-one, 2-hydroxy-1-{4-[4-(2-hydroxy-2-methyl-propionyl)-phenoxy]-phenyl}-2-methyl-propan-1-one, 2-methyl-1-(4-methylthiophenyl)-2-morpholinopropane-1-one, 2-benzyl-2-dimethylamino-1-(4-morpholinophenyl)-butane-1-one, and (2-(dimethylamino)-2-[(4-methylphenyl)methyl]-1-[4-(4-morpholinyl)phenyl]-1-butanone).

[0240] Examples of O-acyloxime ester photoinitiators are 1,2-octanedione, 1-[4-(phenylthio)phenyl]-2-(O-benzoyloxime), ethanone 1-[9-ethyl-6-(2-methylbenzoyl)-9H-carbazole-3-yl]1-(O-acetyloxime) or those described in GB 2339571.

[0241] Examples of acylphosphine photoinitiators include, but are not limited to, bis(2,4,6-trimethylbenzoyl)phenylphosphine oxide, bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl phosphine oxide, bis(2,4,6-trimethylbenzoyl)-(2,4-dipentyloxyphenyl), 2,4,6-trimethylbenzoyl-diphenyl phosphine oxide and ethyl(2,4,6-trimethylbenzoyl)phenylphosphinate, Phenyl(2,4,6-trimethylbenzoyl)phosphinic acid, glycerol ethoxylated trimer (Omnipol® TP from IGM Resins B.V.).

[0242] Examples of the halomethyltriazines based photoinitiators are 2-[2-(4-methoxy-phenyl)-vinyl]-4,6-bis-trichloromethyl[1,3,5]triazine, 2-(4-methoxy-phenyl)-4,6-bis-trichloromethyl[1,3,5]triazine, 2-(3,4-dimethoxyphenyl)-4,6-bis-trichloromethyl[1,3,5]triazine, 2-methyl-4,6-bis-trichloromethyl[1,3,5]triazine.

[0243] Cationic photoinitiators can be also used as the further photoinitiators, when the

photopolymerizable compositions according to the invention are used in hybrid systems (which in this connection mean mixtures of free-radically and cationically curing systems). Examples of suitable cationic photoinitiators are aromatic sulfonium, phosphonium or iodonium salts, as described e.g. in U.S. Pat. No. 4,950,581, or cyclopentadienylarene-iron (II) complex salts, e.g. (η .sup.6-isopropylbenzene) (η .sup.5-cyclopentadienyl) iron (II) hexafluorophosphate or photolabile acids based on oximes, as described, for example, in GB 2 348 644, U.S. Pat. Nos. 4,450,598, 4,136,055, WO 00/10972 and WO 00/26219.

[0244] Any pigment known to the person skilled in the art may be used in the photopolymerizable composition.

[0245] Depending upon the intended use, both inorganic and organic pigments may be used. Such additives are well known to the person skilled in the art; some examples are carbon black, iron oxides, such as iron oxide yellow, iron oxide red, chromium yellow, chromium green, nickel titanium yellow, ultramarine blue, cobalt blue, bismuth vanadate, cadmium yellow and cadmium red. Examples of organic pigments are mono- or bis-azo pigments, and also metal complexes thereof, phthalocyanine pigments, polycyclic pigments, e.g. perylene, anthraquinone, thioindigo, quinacridone or triphenylmethane pigments, and also diketo-pyrrolo-pyrrole, isoindolinone, e.g. tetrachloroisoindolinone, isoindoline, dioxazine, benzimidazolone and quinophthalone pigments. The pigments may be used in the formulations individually or in admixture

[0246] The addition of binders is particularly advantageous when the ethylenically unsaturated, free-radical polymerizable compound(s) are liquid or viscous substances. The choice of binder is made in accordance with the field of use and the properties required therefor, such as developability in aqueous and organic solvent systems, adhesion to substrates and sensitivity to oxygen. Suitable binders are, for example, polymers having a weight average molecular weight (Mw) of approximately from 5,000 Da to 2,000,000 Da, preferably from 10,000 Da to 1,000,000 Da. Illustrative examples are: homo- and copolymers of acrylates and methacrylates, e.g. copolymers of methyl methacrylate/ethyl acrylate/methacrylic acid, poly(methacrylic acid alkyl esters), poly(acrylic acid alkyl esters); cellulose esters and ethers, such as cellulose acetate, cellulose acetate butyrate, methylcellulose, ethylcellulose, polyvinylbutyral, polyvinylformal, cyclised rubber, polyethers such as polyethylene oxide, polypropylene oxide, polytetrahydrofuran, polystyrene, polycarbonates, polyurethanes, chlorinated polyolefins, e.g. polyvinyl chloride, copolymers of vinyl chloride/vinylidene chloride, copolymers of vinylidene chloride with acrylonitrile, methyl methacrylate and vinyl acetate, polyvinyl acetate, copoly (ethylene/vinyl acetate), polymers such as polycaprolactam and poly(hexamethylene adipamide), polyesters such as poly(ethylene glycol terephthalate) and poly(hexamethylene glycol succinate).

[0247] Suitable examples of co-initiators (also known as accelerators) are alcohols, thiols, thioethers, amines or ethers that have an available hydrogen, bonded to a carbon adjacent to the heteroatom, disulfides and phosphines, e.g. as described in EP 438 123 and GB 2 180 358. Suitable examples of amine accelerators/co-initiators include, but are not limited to, aliphatic, cycloaliphatic, aromatic, aryl-aliphatic, heterocyclic, oligomeric or polymeric amines. They can be primary, secondary or tertiary amines, for example butyl amine, dibutyl amine, tributyl amine, cyclohexyl amine, benzyldimethyl amine, di-cyclohexyl amine, N-phenyl glycine, triethyl amine, phenyl-diethanol amine, triethanolamine, piperidine, piperazine, morpholine, pyridine, quinoline, esters of dimethylamino benzoic acid, Michler's ketone (4,4'-bis-dimethyl aminobenzophenone) and derivatives thereof. As the amine accelerators/co-initiators, an amine-modified acrylate compound can be used; examples of such amine-modified acrylate include acrylates modified by reaction with a primary or secondary amine that are described in U.S. Pat. No. 3,844,916, EP 280222, U.S. Pat. No. 5,482,649 or U.S. Pat. No. 5,734,002. Multifunctional amine and polymeric amine derivatives are also suitable as co-initiators some examples are Omnipol® ASA from IGM Resins B.V., Genopol® AB-2 from Rahn A.G., Speedcure® 7040 from Lambson Limited or those described in US2013/0012611

[0248] The choice of additives is governed by the field of use in question and the properties desired for that field. Typical additives include thermal initiators, stabilizers, light stabilizers, fillers, colorants, antistatic agents, wetting agents, flow improvers, and adhesion enhancers.

[0249] For instance, especially in the case of pigmented compositions, the composition may also comprise, as additional additive, a thermal initiator, a compound that forms free radicals when heated, e.g. an azo compounds, such as 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile), a triazene, diazosulfide, pentazadiene or a peroxy compound, for example a hydroperoxide or peroxycarbonate, e.g. tert-butyl hydroperoxide, as described e.g. in EP 245 639.

[0250] Suitable stabilizers are, for example, thermal inhibitors, such as hydroquinone, hydroquinone derivatives, p-methoxyphenol, β -naphthol or sterically hindered phenols, e.g. 2,6-di(tert-butyl)-p-cresol, which prevent premature polymerization. In order to increase dark storage stability it is possible to use, for example, copper compounds, such as copper naphthenate, stearate or octoate, phosphorus compounds, for example triphenylphosphine, tributylphosphine, triethyl phosphite, triphenyl phosphite or tribenzyl phosphite, quaternary ammonium compounds, e.g. tetramethylammonium chloride or trimethylbenzylammonium chloride, or hydroxylamine derivatives, e.g. N,N-diethylhydroxylamine. For the purpose of excluding atmospheric oxygen during polymerization it is possible to add paraffin or similar wax-like substances which, being insoluble in the polymer, migrate to the surface at the beginning of the polymerization and form a transparent surface layer which prevents air from entering.

[0251] It is also possible to add a light stabilizer, such as UV absorbers, e.g. hydroxyphenylbenzotriazole, hydroxyphenylbenzophenone, oxalic acid amide or hydroxyphenyl-s-triazine type. Such components can be used on their own or in the form of mixtures, with or without the use of sterically hindered amines (HALS).

[0252] All fallback positions and preferable embodiments of the photoinitiator package described above or below are applicable mutatis mutandis to the photopolymerizable composition according to the present aspect.

Method

[0253] In a third aspect, the present invention is directed to a method for photocuring photopolymerizable compositions, coatings, adhesives and inks, said method comprising the following steps in the given order: [0254] a) coating or printing the photopolymerizable composition according to the second aspect onto a substrate, and [0255] b) photopolymerizing said coated or printed composition with a light source on said substrate.

[0256] Preferably the light source operates in the near-UV or visible range of the EM-spectrum.

[0257] All fallback positions and preferable embodiments of the photoinitiator package and the photopolymerizable composition described above or below are applicable mutatis mutandis to the method for photocuring photopolymerizable compositions, coatings, adhesives and inks according to the present aspect.

Use

[0258] In a final aspect, the present invention is directed to a use of the photoinitiator package according to the first aspect in the production of printing inks, screen-printing inks, gravure printing inks, solder masks, etch offset-printing inks, flexographic-printing inks, gravure printing inks, ink jet inks, resist material, insulators, encapsulants, image-recording material, solder mask, passivation layer, protective coating, 3D-printing objects and molds, holographic applications, optical fiber coating, waveguide and lens, overprint varnish, wood, vinyl, metal and plastic coatings.

[0259] All fallback positions and preferable embodiments of the photoinitiator package described above or below are applicable mutatis mutandis to the use according to the present aspect.

EXAMPLES

A. Determination Methods

[0260] Tack-free measurement: Tack-free refers to a coating condition whereby a coating is

[0287] The data in Table 2b further reinforces the conclusions drawn from Table 2a, with IE5 to IE9 all demonstrating improved surface cures (relative to RE5) observed despite the lower amounts of photoinitiator, with a 4:1 blend ratio (IE6) being particularly effective, as was the use of the benzoxazole-based sensitizer S2 (IE9). Similar effects can be seen by comparing IE10 to IE14 with RE6 and RE7. Again, the use of amines is shown to be particularly beneficial (IE8 vs IE7, IE14, vs IE10, IE15 vs IE10, IE16 vs IE11, and IE17 vs IE13).

[0288] The photopolymerizable package of the invention can be also prepared in the form of liquid blend. In a 3-necked round-bottomed flask was charged under stirring the photoinitiator and the temperature was slowly increased to 60° C. Then, the sensitizer and the amine (if present—see Table 3) were added, and the solution stirred for another 1 hour at 80° C. Then, the clear solution is slowly cooled at room temperature to yield the liquid blend, which may be used directly for preparing a polymerizable composition.

[0289] As can be seen from Table 3, the inventive photoinitiator packages are present in a liquid form, whilst those using the comparative photoinitiators cannot be prepared as such. The liquid blend is preferable as this avoids any problems associated with dissolving the package during preparation of the photopolymerizable composition and shortens the time needed to prepare said compositions.

[0291] Photopolymerizable compositions (i.e. formulations comparable to those in Table 2) were prepared by adding the photopolymerizable monomer blend M, the photoinitiator package in the form of liquid blend at room temperature. The formulations were stirred at 40° C. for 1 hour and after cooling at room temperature were spread, with a thickness of 12 microns, on a varnished cardboard using a bar-coater, before being photopolymerized using a light source in the same manner as in Table 3 above.

[0292] Formulations equivalent to IE1, IE3, IE5 and IE6 were prepared in this manner (i.e. by mixing IE18, IE19, IE20, or IE21 with M-i or M-ii in the appropriate ratio) and the results in the surface curing evaluation were identical to those reported in Table 3, demonstrating that the method by which the photopolymerizable composition is prepared is not critical in this instance, with the liquid blends being preferred simply for procedural economy.

1. A photoinitiator package comprising: a) one or more bisacylphosphine oxide photoinitiators, each having a structure according to formula (I): ##STR00014## wherein each instance of R is independently selected from the group consisting of C.sub.1-C.sub.4 alkyl; wherein X is selected from the group consisting of direct single bond, O, S, NR.sup.3, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—; wherein R.sup.1 is selected from the group consisting of C.sub.1-C.sub.40 alkyl and interrupted C.sub.2-C.sub.40 alkyl being interrupted by one or more O or C.sub.3-C.sub.8 cycloalkylene, wherein said C.sub.1-C.sub.40 alkyl or interrupted C.sub.2-

C.sub.40 alkyl may be unsubstituted or substituted by one or more groups selected from OH and R.sup.2; wherein R.sup.2 is ##STR00015## wherein R.sup.3 is selected from the group consisting of hydrogen, (CO)R.sup.4, phenyl, C.sub.1-C.sub.12 alkyl, C.sub.2-C.sub.12 alkyl being interrupted by one or more O, wherein said C.sub.1-C.sub.12 alkyl or interrupted C.sub.2-C.sub.12 alkyl is unsubstituted or substituted by one or more C.sub.3-C.sub.7 cycloalkyl, OH or by NCO, C.sub.3-C.sub.12 cycloalkyl which is unsubstituted or substituted by one or more C.sub.1-C.sub.4 alkyl, C.sub.1-C.sub.4 alkoxy, OH or by NCO; and wherein R.sup.4 is selected from the group consisting of C.sub.1-C.sub.12 alkyl or C.sub.2-C.sub.12 alkyl which is interrupted by one or more O, wherein said C.sub.1-C.sub.12 alkyl or interrupted C.sub.2-C.sub.12 alkyl is unsubstituted or substituted by one or more C.sub.3-C.sub.7-cycloalkyl, OH, NCO or by phenyl which is substituted by NCO; C.sub.3-C.sub.12 cycloalkyl; C.sub.2-C.sub.10 alkenyl which is unsubstituted or substituted by one or more C.sub.1-C.sub.4 alkyl, OH or C.sub.1-C.sub.4 alkoxy; C.sub.6-C.sub.14 aryl which is unsubstituted or substituted by C.sub.1-C.sub.12 alkyl, C.sub.1-C.sub.12 alkoxy, NCO or by NCO-substituted C.sub.1-C.sub.12 alkyl. b) one or more optical brightener sensitizers.

2. The photoinitiator package according to claim 1, wherein each instance of R is Me.

3. The photoinitiator package according to claim 1, wherein X is selected from the group consisting of direct single bond, O, —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—.

4. The photoinitiator package according to claim 1, wherein R.sup.1 is selected from the group consisting of C.sub.1-C.sub.20 alkyl, —(CH.sub.2CH.sub.2O—).sub.nCH.sub.3, and —(CH.sub.2CH.sub.2O—).sub.nH, wherein n is an integer in the range from 1 to 20.

5. The photoinitiator package according to claim 1, wherein R.sup.1 has a structure according to formula (II): ##STR00016## wherein each instance of M is independently selected from (CH.sub.2CH.sub.2O) and (CH.sub.2CH(CH.sub.3)O); wherein each instance of Y is independently selected from hydrogen and C.sub.1-C.sub.4 alkyl; wherein each instance of Z has the structure CH.sub.2(M.sup.1).sub.cR.sup.2; wherein each instance of M.sup.1 is independently selected from (OCH.sub.2CH.sub.2) and (OCH(CH.sub.3)CH.sub.2) wherein a is an integer in the range from 0 to 15; wherein b is an integer in the range from 0 to 6; wherein each instance of c is independently an integer in the range from 0 to 15; wherein m is an integer in the range from 0 to 2; and wherein each instance of X is independently selected from the group consisting of —CH.sub.2CO.sub.2—, and —CH.sub.2CH.sub.2CO.sub.2—.

6. The photoinitiator package according to claim 1, wherein at least one of the one or more optical brightener sensitizers has a structure according to formula (III): ##STR00017## wherein R.sup.3a is selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl, C.sub.6-C.sub.14 aryl, and C.sub.6-C.sub.14 heteroaryl, R.sup.4a is selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl, wherein said C.sub.1-C.sub.10 alkyl may be substituted by one or more fluorine atoms, and OR.sup.1a, and each of R.sup.5a to R.sup.8a is independently selected from the group consisting of hydrogen, halogen, C.sub.1-C.sub.10 alkyl, OR.sup.1a, and NR.sup.2a.sub.2; wherein each instance of R.sup.1a is independently selected from hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, and each instance of R.sup.2a is independently selected from hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, wherein each instance of R.sup.1a to R.sup.8a may optionally be joined to one or more further instances of R.sup.1a to R.sup.8a to form one or more 5-membered or 6-membered rings.

7. The photoinitiator package according to claim 1, wherein at least one of the one or more optical brightener sensitizers has a structure according to formula (IV): ##STR00018## wherein each of R.sup.1b to R.sup.4b is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, wherein R.sup.1b and R.sup.2b may be joined to form a 6-membered saturated or unsaturated ring, which may be substituted by one or more substituents selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl, and wherein R.sup.3b and R.sup.4b may be joined to form a 6-membered ring, which may be substituted by one or more substituents selected from the group consisting of hydrogen, C.sub.1-

C.sub.10 alkyl and C.sub.6-C.sub.14 aryl; and wherein A represents a linking group represented by any of the following formulas (V) to (IX): ##STR00019## wherein each * represents a bonding position of A in each formula.

8. The photoinitiator package according to claim 7, wherein at least one of the one or more optical brightener sensitizers has a structure according to formula (X): ##STR00020## wherein each of R.sup.1c to R.sup.8c is independently selected from the group consisting of hydrogen, C.sub.1-C.sub.10 alkyl and C.sub.6-C.sub.14 aryl.

9. The photoinitiator package according to claim 1, wherein the photoinitiator package comprises: a) an amount in the range from 40 to 99.9 wt.-%, relative to the total weight of the photoinitiator package, of the one or more bisacylphosphine oxide photoinitiators having a structure according to formula (I); b) an amount in the range from 0.1 to 50 wt.-%, relative to the total weight of the photoinitiator package, of the one or more optical brightener sensitizers; and c) optionally, an amount in the range from 1.0 to 45 wt.-%, relative to the total weight of the photoinitiator package, of one or more amines.

10. The photoinitiator package according to claim 1, being present in the form of a blend that is liquid at 25° C. and standard pressure.

11. A photopolymerizable composition, comprising: a) one or more ethylenically unsaturated, free-radical polymerizable compounds; b) the photoinitiator package according to claim 1.

12. The photopolymerizable composition according to claim 11, wherein the photopolymerizable composition comprises: a) an amount in the range from 30 to 99.0 wt.-%, relative to the total weight of the photopolymerizable composition, of the one or more ethylenically unsaturated, free-radical polymerizable compounds; b) an amount in the range from 0.5 to 50 wt.-%, relative to the total weight of the photopolymerizable composition, of the photoinitiator package according to claim 1.

13. The photopolymerizable composition according to claim 11, wherein the photopolymerizable composition further comprises one or more, of the following components: c) an amount in the range from 0.5 to 30 wt.-%, of one or more further photoinitiators, one or more photosensitizers and/or one or more co-initiators; d) an amount in the range from 0.1 to 30 wt.-%, relative to the total weight of the photopolymerizable composition, of one or more pigments; e) an amount in the range from 5.0 to 60 wt.-%, relative to the total weight of the photopolymerizable composition, of one or more binders; and f) an amount in the range from 0.01 to 10 wt.-%, relative to the total weight of the photopolymerizable composition, of one or more additives.

14. A method for photocuring photopolymerizable compositions, coatings, adhesives and inks, said method comprising the following steps in the given order: a) coating or printing the photopolymerizable composition according to claim 11 onto a substrate, and b) photopolymerizing said coated or printed composition with a light source on said substrate.

15. (canceled)
