

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250282993

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Camardello; Samuel Joseph et al.

PHOSPHOR COMPOSITIONS AND DEVICES THEREOF

Abstract

A phosphor composition includes a red phosphor material having a red decay rate and a green phosphor material having a green decay rate. The red phosphor material includes a Mn.sup.4+ doped phosphor of Formula I and a Eu.sup.3+ doped uranium phosphor, and a difference between the red decay rate and the green decay rate is no more than 7 ms, A.sub.xMF.sub.y:Mn.sup.4+ (I), wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7. A device is also provided.

Inventors: Camardello; Samuel Joseph (Ballston Spa, NY), Murphy; James E. (Niskayuna, NY)

Applicant: GE Intellectual Property Licensing, LLC (Niskayuna, NY)

Family ID: 88647021

Appl. No.: 18/862301

Filed (or PCT Filed): April 06, 2023

PCT No.: PCT/US2023/065472

Related U.S. Application Data

us-provisional-application US 63338428 20220504

Publication Classification

Int. Cl.: C09K11/77 (20060101); C01B25/45 (20060101); C09K11/02 (20060101); C09K11/71 (20060101); H10H20/851 (20250101)

U.S. Cl.:

CPC **C09K11/7737** (20130101); **C01B25/45** (20130101); **C09K11/025** (20130101); **C09K11/71** (20130101); **H10H20/8513** (20250101); **H10H20/8515** (20250101); C01P2002/54 (20130101); C01P2002/72 (20130101); C01P2006/60 (20130101)

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS [0001] This application claims the priority benefit of U.S. Provisional Patent Application Ser. No. 63/338,428 filed May 4, 2022, which is hereby incorporated by reference in its entirety.

BACKGROUND

[0002] The field of the invention relates generally to phosphor compositions and devices, and more particularly to devices and displays presenting good brightness, large color gamut and reduced lag time.

[0003] Current display device technology relies on liquid crystal displays (LCDs), which is one of the most widely used flat panel displays for industrial and residential applications. Next-generation devices will have low energy consumption, compact size, and high brightness, requiring larger color gamut coverage. Smaller LEDs, such as mini-LEDs or micro-LEDs, will be needed for next-generation devices. Mini-LEDs have a size of about 100 μm to 0.7 mm and micro-LEDs have sizes smaller than 100 μm . Displays may include miniaturized backlighting arrayed with individual mini-LEDs or micro-LEDs, or displays may be without LCDs and include self-emissive phosphor converted (PC) mini-LEDs or micro-LEDs.

[0004] White light can be generated by employing a near-ultraviolet (UV) or blue emitting LED in conjunction with an inorganic phosphor or a blend of inorganic phosphors, such as red-emitting phosphors and green or yellow-green emitting phosphors. The total emission from the phosphor and the LED chip provides a color point with corresponding color coordinates (x and y on the 1931 CIE chromaticity diagram) and correlated color temperature (CCT), and its spectral distribution provides a color rendering capability, measured by the color rendering index (CRI) based on a scale of 100.

[0005] Ideally, phosphors employed in blends for display applications will have similar decay times. Mismatches in phosphor decay times between phosphors in a phosphor blend can cause color shifts and can result in display lag, blurring of the display and ghosting.

[0006] Some next-generation devices, such as PC micro-LEDs are self-emissive and do not require an LCD. These devices and displays can have faster response times and phosphors with faster decay times are desired. Mismatches between phosphor decay times in devices without LCDs can be more of a concern.

BRIEF DESCRIPTION

[0007] In one aspect, a phosphor composition includes a red phosphor material having a red decay rate and a green phosphor material having a green decay rate, wherein the red phosphor material includes a Mn.sup.4+ doped phosphor of Formula I and a Eu.sup.3+ doped uranium phosphor, and wherein a difference between the red decay rate and the green decay rate is no more than 7 ms,

A.sub.xMF.sub.y:Mn.sup.4+ (I),

wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7.

[0008] In another aspect, a device includes an LED light source optically coupled and/or

radiationally connected to a phosphor composition, wherein the phosphor composition includes a red phosphor material having a red decay rate and a green phosphor material having a green decay rate, wherein the red phosphor material includes a Mn.sup.4+ doped phosphor of formula I and a Eu.sup.3+ doped uranium phosphor, and wherein a difference between the red decay rate and the green decay rate is no more than 7 ms,

A.sub.xMF.sub.y:Mn.sup.4+ (I),

wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] FIG. 1 is a schematic cross-sectional view of a device, in accordance with one embodiment of the disclosure.

[0010] FIG. 2 is a schematic cross-sectional view of a lighting apparatus, in accordance with one embodiment of the disclosure.

[0011] FIG. 3 is a schematic cross-sectional view of a lighting apparatus, in accordance with another embodiment of the disclosure.

[0012] FIG. 4 is a cutaway side perspective view of a lighting apparatus, in accordance with one embodiment of the disclosure.

[0013] FIG. 5 is a schematic perspective view of a surface-mounted device (SMD), in accordance with one embodiment of the disclosure.

[0014] FIG. 6 shows the XRD powder pattern for gamma-Ba.sub.2UO.sub.2(PO.sub.4).sub.2.

[0015] FIG. 7 is a spectra graph of emission wavelength (nm) vs. emission intensity for the DU-Red sample and the NFS sample as provided in Example 1.

[0016] FIG. 8 is a spectra graph of emission wavelength (nm) vs. emission intensity for the combination of the DU-Red and the NFS samples as provided in Example 1

DETAILED DESCRIPTION

[0017] In the following specification and the claims, reference will be made to a number of terms, which shall be defined to have the following meanings.

[0018] The singular forms “a”, “an”, and “the” include plural references unless the context clearly dictates otherwise.

[0019] Approximating language, as used herein throughout the specification and claims, may be applied to modify any quantitative representation that could permissibly vary without resulting in a change in the basic function to which it is related. Accordingly, a value modified by a term or terms, such as “about,” “substantially,” and “approximately,” are not to be limited to the precise value specified. In at least some instances, the approximating language may correspond to the precision of an instrument for measuring the value. Here and throughout the specification and claims, range limitations may be combined and/or interchanged, such ranges are identified and include all the sub-ranges contained therein unless context or language indicates otherwise. All references are incorporated herein by reference.

[0020] Square brackets in the formulas indicate that at least one of the elements within the brackets is present in the phosphor material, and any combination of two or more thereof may be present, as limited by the stoichiometry of the composition. For example, the formula

[Ca,Sr,Ba].sub.3MgSi.sub.2O.sub.8:Eu.sup.2+,Mn.sup.2+ encompasses at least one of Ca,Sr or Ba or any combination of two or more of Ca, Sr or Ba. Examples include

Ca.sub.3MgSi.sub.2O.sub.8:Eu.sup.2+, Mn.sup.2+; Sr.sub.3MgSi.sub.2O.sub.8:Eu.sup.2+,

Mn.sup.2+; or Ba.sub.3MgSi.sub.2O.sub.8:Eu.sup.2+, Mn.sup.2+ Formula with an activator after a colon “:” indicates that the phosphor composition is doped with the activator. Formula showing more than one activator separated by a “,” after a colon “:” indicates that the phosphor composition is doped with either activator or both activators. For example, the formula [Ca,Sr,Ba].sub.3MgSi.sub.2O.sub.8:Eu.sup.2+, Mn.sup.2+ encompasses [Ca,Sr,Ba].sub.3MgSi.sub.2O.sub.8:Eu.sup.2+, formula [Ca,Sr,Ba].sub.3MgSi.sub.2O.sub.8:Mn.sup.2+ or formula [Ca,Sr,Ba].sub.3MgSi.sub.2Og:Eu.sup.2+ and Mn.sup.2+.

[0021] Devices and displays can employ light emitting diodes (LEDs) to create a white light, which can be generated with a near-ultraviolet (UV) or blue emitting LED in conjunction with a blend of red-emitting phosphors and green or yellow-green emitting phosphors. In a blend of phosphors there can be a mismatch in the decay rates or times of the phosphors and this mismatch can affect displays and may cause blurring, a display lag and ghosting, particularly in faster display devices that are self-emissive and do not require LCDs (liquid crystal displays), such as PC (phosphor converted) micro-LED displays.

[0022] Narrow band red-emitting phosphors, such as phosphors based on complex fluoride materials activated by Mn.sup.4+ are desired for their large color gamut and good quantum efficiency properties. The inventors have discovered that a red phosphor material, which includes a complex fluoride material activated by Mn.sup.4+ and a Eu.sup.3+ doped uranium phosphor, and a green phosphor material minimizes a mismatch in decay times, while maintaining a large color gamut, brightness and good quantum efficiency.

[0023] In one aspect, a phosphor composition includes a red phosphor material having a red decay rate and a green phosphor material having a green decay rate, wherein the red phosphor material includes a Mn.sup.4+ doped phosphor of Formula I and a Eu.sup.3+ doped uranium phosphors, and wherein a difference between the red decay rate and the green decay rate is no more than 7 ms,

A.sub.xMF.sub.y:Mn.sup.4+ (I),

wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7.

[0024] The red phosphor material blends a Mn.sup.4+ doped phosphor of Formula I and a Eu.sup.3+ doped uranium phosphor. The Mn.sup.4+ doped phosphor of formula I is a narrow band red-emitting phosphor based on complex fluoride materials activated by Mn.sup.4+. Suitable red-emitting phosphors based on complex fluoride materials and processes for making the phosphors are described in U.S. Pat. Nos. 7,497,973, 7,648,649, 8,906,724, 8,252,613, 9,698,314, US 2016/0244663, US Publication No. 2018/0163126, and US Publication No. 2020/0369956. The entire contents of each of which are incorporated herein by reference.

[0025] The red phosphor material includes Mn.sup.4+ doped phosphors of formula I

A.sub.x(MF.sub.y):Mn.sup.+4 (I)

wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is the absolute value of the charge of the (MF.sub.y) ion; and y is 5, 6 or 7.

[0026] Examples of the red-emitting phosphors of formula I include, but are not limited to, K.sub.2(SiF.sub.6):Mn.sup.4+, K.sub.2(TiF.sub.6):Mn.sup.4+, K.sub.2(SnF.sub.6):Mn.sup.4+, Cs.sub.2(TiF.sub.6):Mn.sup.4+, Rb.sub.2(TiF.sub.6):Mn.sup.4+, Cs.sub.2(SiF.sub.6):Mn.sup.4+, Rb.sub.2(SiF.sub.6):Mn.sup.4+, Na.sub.2(TiF.sub.6):Mn.sup.4+, Na.sub.2(SiF.sub.6):Mn.sup.4+, Na.sub.2(ZrF.sub.6):Mn.sup.4+, K.sub.3(ZrF.sub.7):Mn.sup.4+, K.sub.3(BiF.sub.7):Mn.sup.4+, K.sub.3(YF.sub.7):Mn.sup.4+, K.sub.3(LaF.sub.7):Mn.sup.4+, K.sub.3(GdF.sub.7):Mn.sup.4+, K.sub.3(NbF.sub.7):Mn.sup.4+, and K.sub.3(TaF.sub.7):Mn.sup.4+.

[0027] The amount of activator Mn incorporation in the Mn.sup.4+ doped phosphors (referred to as Mn %) improves color conversion. Increasing the amount of Mn % incorporation improves color conversion by increasing the intensity of the red emission, maximizing absorption of excitation blue light and reducing the amount of unconverted blue light or bleed-through of blue light from a blue LED.

[0028] In one embodiment, the red-emitting Mn.sup.4+ doped phosphor has a Mn loading or Mn % of at least 1 wt %. In another embodiment, the red-emitting phosphor has a Mn loading of at least 1.5 wt %. In another embodiment, the red-emitting phosphor has a Mn loading of at least 2 wt %. In another embodiment, the red-emitting phosphor has a Mn % of at least 3 wt %. In another embodiment the Mn % is greater than 3.0 wt %. In another embodiment, the content of Mn in the red-emitting phosphor is from about 1 wt % to about 4 wt %. In another embodiment, the red-emitting phosphor has a Mn % from about 2 wt % to about 5 wt %.

[0029] In one embodiment, the Mn.sup.4+ doped phosphor may be a manganese-doped potassium fluorosilicate, such as K.sub.2SiF.sub.6:Mn.sup.4+ (PFS). PFS has a narrow band emission having multiple peaks with an average full width at half maximum (FWHM) of less than 4 nm. In another embodiment, the red-emitting phosphor may be Na.sub.2SiF.sub.6:Mn.sup.4+ (NFS).

[0030] In one embodiment, Mn.sup.4+ doped phosphors may be further treated, such as by annealing, wash treatment, roasting or any combination of these treatments. Post-treatment processes for Mn.sup.4+ doped phosphors are described in U.S. Pat. Nos. 8,906,724, 8,252,613, 9,698,314, US Publication No. 2016/0244663, US Publication No. 2018/0163126, and US Publication No. 2020/0369956. The entire contents of each of which are incorporated herein by reference. In one embodiment, the Mn.sup.4+ doped phosphors may be annealed, treated with multiple wash treatments and roasted.

[0031] To improve reliability, the Mn.sup.4+ doped phosphor of Formula I may be at least partially coated with surface coatings to enhance stability of the phosphor particles and resist aggregation by modifying the surface of the particles and increase the zeta potential of the particles. In one embodiment, the surface coatings may be a metal fluoride, silica or organic coating. In one embodiment, the red-emitting phosphors based on complex fluoride materials activated by Mn.sup.4+ phosphors are at least partially coated with a metal fluoride, which increases positive Zeta potential and reduces agglomeration. In one embodiment, the metal fluoride coating includes MgF.sub.2, CaF.sub.2, SrF.sub.2, BaF.sub.2, AgF, ZnF.sub.2, AlF.sub.3 or a combination thereof. In another embodiment, the metal fluoride coating is in an amount from about 0.1 wt % to about 10 wt %. In another embodiment, the metal fluoride coating is present in an amount from about 0.1 wt % to about 5 wt %. In another embodiment, the metal fluoride coating is present from about 0.3 wt % to about 3 wt %. Metal fluoride coated red-emitting phosphors based on complex fluoride materials activated by Mn.sup.4+ are prepared as described in WO 2018/093832, US Publication No. 2018/0163126 and US Publication No. 2020/0369956. The entire contents of each of which are incorporated herein by reference.

[0032] A Eu.sup.3+ doped uranium phosphor has a narrow band emission and is a uranium phosphor in which an energy transfer occurs from the uranium ion to the Europium ion. The energy transfer results in a color shift by the phosphor as measured by a difference in color coordinates ccx and ccy on the CIE chromaticity diagram.

[0033] In some embodiments, the Eu.sup.3+ doped uranium phosphor has formula IIA or IIB:

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3:Eu.sup.3+ (IIA)

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3:Eu.sup.3+

and A (IIB)
 wherein $0 \leq a \leq 1$, $0 \leq b \leq 1$, $0.75 \leq x \leq 1.25$, $0.75 \leq y \leq 1.25$, $0.75 \leq z \leq 1.25$ and A is Li.sup.+, Na.sup.+, K.sup.+, Rb.sup.+, Cs.sup.+, or mixtures thereof. Particular examples include Ba[Mg,Zn]UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+, and more particularly, BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Li.sup.+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Na.sup.+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and K.sup.+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Rb.sup.+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Cs.sup.+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Li.sup.+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Na.sup.+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and K.sup.+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Rb.sup.+; and BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Cs.sup.+. Uranium phosphors having formula IIA or IIB exhibit an orange, orange/red or red emission.
 [0034] In some embodiments, the Eu.sup.3+ doped uranium phosphor has formula IIIA or IIIB:

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.(2p+2q+5r)/2:Eu.sup.3+ (IIIA)

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.(2p+2q+5r)/2:Eu.sup.3+ and A (IIIB)
 wherein $0 \leq a \leq 1$, $0 \leq b \leq 1$, $2.5 \leq p \leq 3.5$, $1.75 \leq q \leq 2.25$, $3.5 \leq r \leq 4.5$ and A is Li.sup.+, Na.sup.+, K.sup.+, Rb.sup.+, Cs.sup.+, or mixtures thereof. Particular examples include Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Li.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Na.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and K.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Rb.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Cs.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Li.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Na.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and K.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Rb.sup.+; Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Cs.sup.+; γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+; γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Li.sup.+; γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Na.sup.+; γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and K.sup.+; γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Rb.sup.+; and γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Cs.sup.+. In one embodiment, when the formula is [Ba], p is 3.5, q is 1.75, [P] and r is 3.5, the base compound is Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and A and the compound is in the gamma phase. In another embodiment, when the formula is Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and A, the phosphor is in the gamma phase and is γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and A. Phosphor gamma phase Ba₂UO₂(PO₄)₂ described in PCT Publication No. WO 2021/211600, which is incorporated herein by reference. Gamma phase Ba.sub.2UO.sub.2(PO.sub.4).sub.2 or γ -Ba.sub.2UO.sub.2(PO.sub.4).sub.2 having an XRD powder pattern as shown in FIG. 6. Uranium phosphors having formula IIIA or IIIB exhibit an orange, orange/red or red emission.
 [0035] In other embodiments the Eu.sup.3+ doped uranium phosphor has formula IV:

$A_{2}UO_{2}(P,V)_{2}O_{7}Eu^{3+}$ (IV)

where A is Li, Na, K, Rb, Cs, or a combination thereof. Particular examples include

$A_{2}UO_{2}P_{2}O_{7}Eu^{3+}$ and more particularly,

$Na_{2}UO_{2}P_{2}O_{7}Eu^{3+}$ and $K_{2}UO_{2}P_{2}O_{7}Eu^{3+}$.

Uranium phosphors having formula IV exhibit an orange, orange/red or red emission.

[0036] In one embodiment, the Eu^{3+} doped uranium phosphor includes a Europium ion, Eu^{3+} in an amount of from about 0.001 to about 10 mole percent. In another embodiment, the Europium ion may be present in an amount of from about 0.01 mole percent to about 10 mole percent. In another embodiment, the Europium ion may be present in an amount from about 0.1 mole percent to about 10 mole percent. In another embodiment, the Europium ion may be present in an amount from about 0.5 to about 5 mole percent. In another embodiment, the Europium ion may be present from about 1 to about 3 mole percent. In another embodiment, the Europium ion may be present from about 0.01 mole percent to about 1 mole percent. In another embodiment, the Europium ion may be present from about 0.05 mole percent to about 1 mole percent. In another embodiment, the Europium ion may be present from about 0.1 mole percent to about 1 mole percent. In another embodiment, the Europium ion may be present from about 0.5 mole percent to about 1 mole percent.

[0037] In some embodiments, the Eu^{3+} doped uranium phosphor includes one or more alkali metal ions, such as Li^{+} , Na^{+} , K^{+} , Rb^{+} , Cs^{+} , or mixtures thereof. The alkali metal ion may be present in an amount from about 0.01 mole percent to about 10 mole percent. In one embodiment, the alkali metal ion may be present in an amount of from about 0.1 to about 10 molar percent. In another embodiment, the alkali metal ion may be present in an amount of from about 0.5 to about 5 mole percent. In another embodiment, the alkali metal ion may be present from about 1 to about 3 mole percent. In another embodiment, the alkali metal ion may be present from about 0.01 mole percent to about 1 mole percent. In another embodiment, the alkali metal ion may be present from about 0.05 mole percent to about 1 mole percent. In another embodiment, the alkali metal ion may be present from about 0.1 mole percent to about 1 mole percent. In another embodiment, the alkali metal ion may be present from about 0.5 mole percent to about 1 mole percent.

[0038] In one embodiment, the Eu^{3+} doped uranium phosphor is

$Na_{2}UO_{2}P_{2}O_{7}Eu^{3+}$. $Na_{2}UO_{2}P_{2}O_{7}Eu^{3+}$ has a narrow band red emission with a peak emission at 618 nm.

$Na_{2}UO_{2}P_{2}O_{7}Eu^{3+}$ can absorb blue light from a blue LED completely and fully convert blue light.

[0039] The Eu^{3+} doped uranium phosphors of the present disclosure may be produced by firing a mixture of precursors under an oxidizing atmosphere. Non-limiting examples of suitable precursors include the appropriate metal oxides, hydroxides, alkoxides, carbonates, nitrates, aluminates, silicates, citrates, oxalates, carboxylates, tartarates, stearates, nitrites, peroxides, phosphates, pyrophosphates, alkali salts and combinations thereof. Suitable materials for use as precursors include, but are not limited to, $BaCO_{3}$, $BaHPO_{4}$, $Ba_{3}(PO_{4})_{2}$, $Ba_{2}P_{2}O_{7}$, $Ba_{2}Zn(PO_{4})_{2}$, $BaZnP_{2}O_{7}$, $Ba(OH)_{2}$, $Ba(C_{2}O_{4})$, $Ba(C_{2}H_{3}O_{2})_{2}$, $Ba_{3}(C_{6}H_{5}O_{7})_{2}$, $Ba(NO_{3})_{2}$, $CaCO_{3}$, $Cs_{2}CO_{3}$, $HUO_{2}PO_{4} \cdot 4H_{2}O$, $KH_{2}PO_{4}$, $K_{2}HPO_{4}$, $K_{2}CO_{3}$, $Li_{2}CO_{3}$, $Li_{2}HPO_{4}$, $LiH_{2}PO_{4}$, $Mg(C_{2}O_{4})$, $Mg(C_{2}H_{3}O_{2})_{2}$, $Mg(C_{6}H_{6}O_{7})$, $MgCO_{3}$, MgO , $Mg(OH)_{2}$, $Mg_{3}(PO_{4})_{2}$, $Mg_{2}P_{2}O_{7}$, $Mg_{2}Ba(PO_{4})_{2}$, $MgHPO_{4}$, $Mg(NO_{3})_{2}$, $NaH_{2}PO_{4}$, $Na_{2}HPO_{4}$, $Na_{2}CO_{3}$, $NH_{4}MgPO_{4}$, $(NH_{4})_{2}HPO_{4}$, $NH_{4}VO_{3}$, $Rb_{2}CO_{3}$, $SrCO_{3}$,

Zn(C.sub.2O.sub.4), Zn(C.sub.2H.sub.3O.sub.2).sub.2, Zn.sub.3(C.sub.6H.sub.5O.sub.7).sub.2, ZnCO.sub.3, ZnO, Zn(OH).sub.2, Zn.sub.3(PO.sub.4).sub.2, Zn.sub.2P.sub.2O.sub.7, Zn.sub.2Ba(PO.sub.4).sub.2, ZnHPO.sub.4, Zn(NO.sub.3).sub.2, NH.sub.4ZnPO.sub.4, UO.sub.2, UO.sub.2(NO.sub.3).sub.2, (UO.sub.2).sub.2P.sub.2O.sub.7, (UO.sub.2).sub.3(PO.sub.4).sub.2, NH.sub.4 (UO.sub.2)PO.sub.4, UO.sub.2CO.sub.3, UO.sub.2(C.sub.2H.sub.3O.sub.2).sub.2, UO.sub.2(C.sub.2O.sub.4), H(UO.sub.2)PO.sub.4, UO.sub.2(OH).sub.2, and ZnUO.sub.2(C.sub.2H.sub.3O.sub.2).sub.4, and various hydrates. For example, the exemplary phosphor BaZnUO.sub.2(PO.sub.4).sub.2 may be produced by mixing the appropriate amounts of BaCO.sub.3, ZnO, and UO.sub.2 with the appropriate amount of (NH.sub.4).sub.2HPO.sub.4 and then firing the mixture under an air atmosphere. The precursors may be in solid form or in solution. Non-limiting examples of solvents include water, ethanol, acetone, and isopropanol, and suitability depends chiefly on solubility of the precursors in the solvent. After firing, the phosphor may be milled to break up any agglomerates that may have formed during the firing procedure.

[0040] The mixture of starting materials for producing the Eu.sup.3+ doped uranium phosphor includes, but is not limited to, Eu.sub.2O.sub.3 or EuPO.sub.4.

[0041] The mixture of starting materials for producing the phosphor may also include one or more low melting temperature flux materials, such as boric acid, borate compounds such as lithium tetraborate, alkali phosphates, and combinations thereof. Non-limiting examples include (NH.sub.4).sub.2HPO.sub.4 (DAP), Li.sub.3PO.sub.4, Na.sub.3PO.sub.4, NaBO.sub.3—H.sub.2O, Li.sub.2B.sub.4O.sub.7, K.sub.4P.sub.2O.sub.7, Na.sub.4P.sub.2O.sub.7, H.sub.3BO.sub.3, and B.sub.2O.sub.3. The flux may lower the firing temperature and/or firing time for the phosphor. If a flux is used, it may be desirable to wash the final phosphor product with a suitable solvent to remove any residual soluble impurities that may have originated from the flux.

[0042] The firing of the samples is generally done in air, but since the uranium is in its highest oxidation state (U.sup.6+) it can also be fired in O.sub.2 or other wet or dry oxidizing atmospheres, including at oxygen partial pressures above one atmosphere, at a temperature between about 300° C. and about 1300° C., particularly between about 500° C. and about 1200° C., for a time sufficient to convert the mixture to the phosphor. The firing time required may range from about one to twenty hours, depending on the amount of the mixture being fired, the extent of contact between the solid and the gas of the atmosphere, and the degree of mixing while the mixture is fired or heated. The mixture may rapidly be brought to and held at the final temperature, or the mixture may be heated to the final temperature at a lower rate such as from about 2° C./minute to about 200° C./minute.

[0043] The red phosphor material blends a narrow band Mn.sup.4+ doped phosphor of Formula I and a narrow band Eu.sup.3+ doped uranium phosphor. The red phosphor material may include additional phosphors with orange, red/orange or red emission (from about 585 nm to about 780 nm). The red phosphor material has a red decay rate, which is the weighted average of the decay rate for each of the phosphors in the red phosphor material, based on the total weight of the red phosphor material. In one embodiment, the decay rate of the red phosphor material is the weighted average of a decay rate of the Mn.sup.4+ doped phosphor of formula I and a decay rate of the Eu.sup.3+ doped uranium phosphors, based on the total weight of the red phosphor material. In another embodiment, when the red phosphor material includes one or more additional phosphors with orange, red/orange or red emissions, the red decay rate is the weighted average of a decay rate of the Mn.sup.4+ doped phosphor of formula I, a decay rate of the Eu.sup.3+ doped uranium phosphor, and one or more decay rate(s) for the one or more additional phosphors, based on the total weight of the red phosphor material.

[0044] In one embodiment, the red phosphor material includes from about 1 weight percent to about 99 weight percent of a Mn.sup.4+ doped phosphor of Formula I and from about 99 weight percent to about 1 weight percent of a Eu.sup.3+ doped uranium phosphor. In another embodiment, the red phosphor material includes from about 10 weight percent to about 90 weight percent of a

material.

[0047] In one embodiment, the red phosphor material includes $\text{Na.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+}$ and $\text{Na}_2\text{SiF}_6\text{:Mn.sup.4+}$ (NFS) In another embodiment, the red phosphor material includes $\text{Na.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+}$ and $\text{K.sub.2SiF.sub.6:Mn.sup.4+}$ (PFS).

[0048] Mn.sup.4+ doped phosphors of formula I have large color gamuts, while Eu.sup.3+ doped uranium phosphors have a smaller color gamut and shorter decay rates than the Mn.sup.4+ phosphors of formula I. Blending the phosphors results in a red phosphor material having a shorter red decay time than a Mn.sup.4+ doped phosphor of formula I, while maintaining a large color gamut.

[0049] The phosphor composition includes a green phosphor material. The green phosphor material includes at least one green-emitting phosphor. The green-emitting phosphor may include any suitable green-emitting phosphor.

[0050] In one embodiment, the green-emitting phosphor may include a narrow-band uranium-based phosphor having formulas V, VI, VII, VIII or IX

$[\text{Ba.sub.1-a-bSr.sub.aCa.sub.b}].\text{sub.x}[\text{Mg,Zn}].\text{sub.y}(\text{UO.sub.2}).\text{sub.z}([\text{P,V}]\text{O.sub.4}).\text{sub.2(x+y+z)/3}$ (V),

$[\text{Ba.sub.1-a-bSr.sub.aCa.sub.b}].\text{sub.p}(\text{UO.sub.2}).\text{sub.q}[\text{P,V}].\text{sub.rO.sub.(2p+2q+5r)/2}$ (VI),

$\text{A.sub.2UO.sub.2 [P,V].sub.2O.sub.7}$ (VII),

$\text{A.sub.4UO.sub.2([P,V]O.sub.4).sub.2}$ (VIII), or

$\text{AUO.sub.2([P,V]O.sub.3).sub.3}$ (IX)

where $0 \leq a \leq 1$, $0 \leq b \leq 1$, $0.75 \leq x \leq 1.25$, $0.75 \leq y \leq 1.25$, $0.75 \leq z \leq 1.25$; $2.5 \leq p \leq 3.5$, $1.75 \leq q \leq 2.25$, $3.5 \leq r \leq 4.5$ and A is Li, Na, K, Rb, Cs, or a combination thereof. These phosphors exhibit a green emission.

[0051] Examples of uranium phosphors include

$\text{Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7}$,

$\text{Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7}$, gamma γ -

$\text{Ba.sub.2UO.sub.2(PO.sub.4).sub.2}$, $\text{BaMgUO.sub.2(PO.sub.4).sub.2}$,

$\text{BaZnUO.sub.2(PO.sub.4).sub.2}$, $\text{Na.sub.2UO.sub.2P.sub.2O.sub.7}$,

$\text{K.sub.2UO.sub.2P.sub.2O.sub.7}$, $\text{Rb.sub.2UO.sub.2P.sub.2O.sub.7}$,

$\text{Cs.sub.2UO.sub.2P.sub.2O.sub.7}$, $\text{K.sub.4UO.sub.2(PO.sub.4).sub.2}$, $\text{KUO.sub.2(VO.sub.4).sub.2}$,

$\text{NaUO.sub.2P.sub.3O.sub.9}$.

[0052] The uranium phosphors may be prepared as shown above for the Eu.sup.3+ doped uranium phosphors without the addition of the Europium starting materials, such as Eu.sub.2O.sub.3 or EuPO.sub.4 .

[0053] In other embodiments, the green phosphor material includes Beta-SiAlON.

[0054] The green phosphor material has a green decay rate, which is the weighted average of the decay rate for each of the phosphors in the green phosphor material, based on the total weight of the green phosphor material.

[0055] The phosphor composition includes a red phosphor material and a green phosphor material. In one embodiment, the composition includes from about 1 weight percent to about 99 weight percent of the red phosphor material and from about 99 weight percent to about 1 weight percent of the green phosphor material. In another embodiment, the composition includes from about 10 weight percent to about 90 weight percent of the red phosphor material and about 90 weight percent to about 10 weight percent of the green phosphor material. In another embodiment, the composition includes from about 20 weight percent to about 80 weight percent of the red phosphor

material and from about 80 weight percent to about 20 weight percent of the green phosphor material. In another embodiment, the composition includes from about 30 weight percent to about 70 weight percent of the red phosphor material and from about 70 weight percent to about 30 weight percent of the green phosphor material. In another embodiment, the composition includes from about 40 weight percent to about 60 weight percent of the red phosphor material and from about 60 weight percent to about 40 weight percent of the green phosphor material. In another embodiment, the composition includes from about 45 weight percent to about 55 weight percent of the red phosphor material and from about 55 weight percent to about 45 weight percent of the green phosphor material. In another embodiment, the composition includes about 50 weight percent of the red phosphor material and about 50 weight percent of the green phosphor material. In another embodiment, the composition includes from about 1 weight percent to about 50 weight percent of the red phosphor material and about 50 weight percent to about 1 weight percent of the green phosphor material. The percentages by weight are based on the total weight of the composition.

[0056] In one embodiment, the phosphor composition includes from about 1 weight percent to about 99 weight percent of the red phosphor material. In another embodiment, the composition includes from about 10 weight percent to about 90 weight percent of the red phosphor material. In another embodiment, the composition includes from about 20 weight percent to about 80 weight percent of the red phosphor material. In another embodiment, the composition includes from about 30 weight percent to about 70 weight percent of the red phosphor material. In another embodiment, the composition includes from about 40 weight percent to about 60 weight percent of the red phosphor material. In another embodiment, the composition includes from about 45 weight percent to about 55 weight percent of the red phosphor material. In another embodiment, the composition includes about 50 weight percent of the red phosphor material. In another embodiment, the composition includes from about 1 weight percent to about 50 weight percent of the red phosphor material. In another embodiment, the composition includes from about 50 weight percent to about 99 weight percent of the red phosphor material. The percentages by weight are based on the total weight of the phosphor composition.

[0057] In one embodiment, the phosphor composition includes from about 1 weight percent to about 99 weight percent of the green phosphor material. In another embodiment, the composition includes from about 10 weight percent to about 90 weight percent of the green phosphor material. In another embodiment, the composition includes from about 20 weight percent to about 80 weight percent of the green phosphor material. In another embodiment, the composition includes from about 30 weight percent to about 70 weight percent of the green phosphor material. In another embodiment, the composition includes from about 40 weight percent to about 60 weight percent of the green phosphor material. In another embodiment, the composition includes from about 45 weight percent to about 55 weight percent of the green phosphor material. In another embodiment, the composition includes about 50 weight percent of the green phosphor material. In another embodiment, the composition includes from about 1 weight percent to about 50 weight percent of the green phosphor material. In another embodiment, the composition includes from about 50 weight percent to about 99 weight percent of the green phosphor material. The percentages by weight are based on the total weight of the phosphor composition.

[0058] Minimizing the decay rate mismatch between the red phosphor material and the green phosphor material in a phosphor composition to less than 7 milliseconds results in a phosphor composition with a reduced color shift and faster response times in displays. In another embodiment, a difference between the red decay rate and the green decay rate is less than 6 milliseconds. In another embodiment, a difference between the red decay rate and the green decay rate is less than 5 milliseconds. In another embodiment, a difference between the red decay rate and the green decay rate is less than 4 milliseconds. In another embodiment, a difference between the red decay rate and the green decay rate is less than 3 milliseconds. In another embodiment, a

difference between the red decay rate and the green decay rate is from about 0 ms to about 7 ms. In another embodiment, a difference between the red decay rate and the green decay rate is from about 0 ms to about 6 ms. In another embodiment, a difference between the red decay rate and the green decay rate is from about 0 ms to about 5 ms. In another embodiment, a difference between the red decay rate and the green decay rate is from about 0 ms to about 4 ms. In another embodiment, a difference between the red decay rate and the green decay rate is from about 0 ms to about 3 ms.

[0059] The phosphors may be in particulate form. In some embodiments, the median particle size of the phosphors may range from about 1 to about 50 microns. In another embodiment, the median particle size may range from about 15 to about 35 microns. In another embodiment, the median particle size may be about 30 microns or less.

[0060] In another embodiment, the phosphors are in particulate form including a monodisperse population of particles having a population of particles including a D50 particle size diameter in the range from about 0.1 μm to about 15 μm . In another embodiment, the particle size diameter is in the range from about 0.1 μm to about 10 μm . In another embodiment, the particle size distribution that is, D50 of less than 15 μm , particularly, D50 of less than 10 μm , particularly D50 of less than 5 μm , or D50 of less than 3 μm , or D50 of less than 2 μm , or D50 of less than 1 μm . In another embodiment, the particle size distribution D50 may be in a range from about 0.1 μm to about 5 μm . In another embodiment, the D50 particle size is in a range from about 0.1 μm to about 3 μm . In another embodiment, the D50 particle size is in a range from about 0.1 μm to about 1 μm . In another embodiment, the D50 particle size is in a range from about 1 μm to about 5 μm . D50 (also expressed as D50) is defined as the median particle size for a volume distribution. D90 or D90 is the particle size for a volume distribution that is greater than the particle size of 90% of the particles of the distribution. D10 or D.sub.10 is the particle size for a volume distribution that is greater than the particle size of 10% of the particles of the distribution. Particle size of the phosphors may be conveniently measured by laser diffraction or optical microscopy methods, and commercially available software can generate the particle size distribution and span. Span is a measure of the width of the particle size distribution curve for a particulate material or powder, and is defined according to the equation:

$$[00001] \text{Span} = \frac{(D_{90} - D_{10})}{D_{50}}$$

wherein D90, D10 and D50 are defined above. For phosphor particles, span of the particle size distribution is not necessarily limited and may be ≤ 1.0 in some embodiments.

[0061] The phosphor composition may include, one or more other luminescent materials.

Additional luminescent materials, such as blue, yellow, red, orange, or other color phosphors may be used in the phosphor composition to customize the white color of the resulting light and produce specific spectral power distributions.

[0062] Suitable phosphors for use in the phosphor composition, include, but are not limited to:

((Sr.sub.1-z[Ca,Ba,Mg,Zn].sub.z).sub.1-(x+w)[Li,Na,K,Rb].sub.wCe.sub.x).sub.3(Al.sub.1-ySi.sub.y)O.sub.4+y+3(x-w)F.sub.1-y-3(x-w), $0 < x \leq 0.10$, $0 \leq y \leq 0.5$, $0 \leq z \leq 0.5$, $0 \leq w \leq x$;

[Ca,Ce].sub.3Sc.sub.2Si.sub.3O.sub.12 (CaSiG); [Sr,Ca,Ba].sub.3Al.sub.1-xSi.sub.xO.sub.4+xF.sub.1-x:Ce.sup.3+ (SASOF));

[Ba,Sr,Ca].sub.5(PO.sub.4).sub.3[Cl,F,Br,OH]:Eu.sup.2+, Mn.sup.2+;

[Ba,Sr,Ca]BPO.sub.5:Eu.sup.2+, Mn.sup.2+;

[Sr,Ca].sub.10(PO.sub.4).sub.6*vB.sub.2O.sub.3:Eu.sup.2+ (wherein $0 < v \leq 1$);

Sr.sub.2Si.sub.3O.sub.8*2SrCl.sub.2:Eu.sup.2+;

[Ca,Sr,Ba].sub.3MgSi.sub.2O.sub.8:Eu.sup.2+,Mn.sup.2+; BaAl.sub.8O.sub.13:Eu.sup.2+;

2SrO*0.84P.sub.2O.sub.5*0.16B.sub.2O.sub.3:Eu.sup.2+;

[Ba,Sr,Ca]MgAl.sub.10O.sub.17:Eu.sup.2+, Mn.sup.2+; [Ba,Sr,Ca] Al.sub.2O.sub.4:Eu.sup.2+;

[Y,Gd,Lu,Sc,La]BO.sub.3:Ce.sup.3+,Tb.sup.3+; ZnS:Cu.sup.+,Cl.sup.-; ZnS:Cu.sup.+, Al.sup.3+;

ZnS:Ag.sup.+, Cl.sup.-; ZnS:Ag.sup.+,Al.sup.3+; [Ba,Sr,Ca].sub.2Si.sub.1-nO.sub.4-2n:Eu.sup.2+ (wherein $0 \leq n \leq 0.2$); [Ba,Sr,Ca].sub.2[Mg,Zn]Si.sub.2O.sub.7:Eu.sup.2+; [Sr,Ca,Ba]

[Al,Ga,In].sub.2S.sub.4:Eu.sup.2+; [Y,Gd,Tb,La,Sm,Pr,Lu].sub.3[Al,Ga].sub.5-aO.sub.12-3/2a:Ce.sup.3+ (wherein $0 \leq a \leq 0.5$); [Ca,Sr].sub.8[Mg,Zn](SiO.sub.4).sub.4Cl.sub.2:Eu.sup.2+,Mn.sup.2+; Na.sub.2Gd.sub.2B.sub.2O.sub.7:Ce.sup.3+,Tb.sup.3+; [Sr,Ca,Ba,Mg,Zn].sub.2P.sub.2O.sub.7:Eu.sup.2+, Mn.sup.2+; [Gd,Y,Lu,La].sub.2O.sub.3:Eu.sup.3+, Bi.sup.3+; [Gd,Y,Lu,La].sub.2O.sub.2S:Eu.sup.3+,Bi.sup.3+; [Gd,Y,Lu,La]VO.sub.4:Eu.sup.3+,Bi.sup.3+; [Ca,Sr,Mg]S:Eu.sup.2+, Ce.sup.3+; SrY.sub.2S.sub.4:Eu.sup.2+; CaLa.sub.2S.sub.4:Ce.sup.3+; [Ba,Sr,Ca]MgP.sub.2O.sub.7:Eu.sup.2+, Mn.sup.2+; [Y,Lu].sub.2WO.sub.6:Eu.sup.3+, Mo.sup.6+; [Ba,Sr,Ca].sub.bSi.sub.gNm:Eu.sup.2+ (wherein $2b+4g=3m$); Ca.sub.3(SiO.sub.4)Cl.sub.2:Eu.sup.2+; [Lu,Sc,Y,Tb].sub.2-u-vCe.sub.vCa.sub.1+uLi.sub.wMg.sub.2-wP.sub.w[Si,Ge].sub.3-wO.sub.12-u/2 (where $0.5 \leq u \leq 1$, $0 < v \leq 0.1$, and $0 \leq w \leq 0.2$); [Y,Lu,Gd].sub.2-m[Y,Lu,Gd]Ca.sub.mSi.sub.4N.sub.6+mC.sub.1-m:Ce.sup.3+, (wherein $0 \leq m \leq 0.5$); [Lu,Ca,Li,Mg,Y], alpha-SiAlON doped with Eu.sup.2+ and/or Ce.sup.3+; Sr(LiAl.sub.3N.sub.4):Eu.sup.2+, [Ca,Sr,Ba] SiO.sub.2N.sub.2:Eu.sup.2+, Ce.sup.3+; beta-SiAlON:Eu.sup.2+; 3.5MgO*0.5MgF.sub.2*GeO.sub.2:Mn.sup.4+; Ca.sub.1-c-fCe.sub.cEu.sub.fAl.sub.1+cSi.sub.1-cN.sub.3, (where $0 \leq c \leq 0.2$, $0 \leq f \leq 0.2$); Ca.sub.1-h-rCe.sub.nEu.sub.rAl.sub.1-h(Mg,Zn).sub.hSiN.sub.3, (where $0 \leq h \leq 0.2$, $0 \leq r \leq 0.2$); Ca.sub.1-2s-tCe.sub.5[Li,Na].sub.sEu.sub.tAlSiN.sub.3, (where $0 \leq s \leq 0.2$, $0 \leq t \leq 0.2$, $s+t > 0$); [Sr,Ca]AlSiN.sub.3; and Eu.sup.2+, Ce.sup.3+, Li.sub.2CaSiO.sub.4:Eu.sup.2+.

[0063] In particular embodiments, additional phosphors include:

[Y,Gd,Lu,Tb].sub.3[Al,Ga].sub.5O.sub.12:Ce.sup.3+, β -SiAlON:Eu.sup.2+, [Sr,Ca,Ba][Ga,Al].sub.2S.sub.4:Eu.sup.2+, [Li,Ca] α -SiAlON:Eu.sup.2+, [Ba,Sr,Ca].sub.2Si.sub.5N.sub.8:Eu.sup.2+, [Ca,Sr]AlSiN.sub.3:Eu.sup.2+, [Ba,Sr,Ca]LiAl.sub.3N.sub.4:Eu.sup.2+, [Sr,Ca,Mg]S:Eu.sup.2+, and [Ba,Sr,Ca].sub.2Si.sub.2O.sub.4:Eu.sup.2+.

[0064] Other additional luminescent materials suitable for use in the phosphor composition may include electroluminescent polymers such as polyfluorenes, preferably poly(9,9-dioctyl fluorene) and copolymers thereof, such as poly(9,9'-dioctylfluorene-co-bis-N,N'-(4-butylphenyl)diphenylamine) (F8-TFB); poly(vinylcarbazole) and polyphenylenevinylene and their derivatives. In addition, the light emitting layer may include a blue, yellow, orange, green or red phosphorescent dye or metal complex, a quantum dot material, or a combination thereof. Materials suitable for use as the phosphorescent dye include, but are not limited to, tris(1-phenylisoquinoline) iridium (III) (red dye), tris(2-phenylpyridine) iridium (green dye) and iridium (III) bis(2-(4,6-difluorephenyl)pyridinato-N,C2) (blue dye). Commercially available fluorescent and phosphorescent metal complexes from ADS (American Dyes Source, Inc.) may also be used. ADS green dyes include ADS060GE, ADS061GE, ADS063GE, and ADS066GE, ADS078GE, and ADS090GE. ADS blue dyes include ADS064BE, ADS065BE, and ADS070BE. ADS red dyes include ADS067RE, ADS068RE, ADS069RE, ADS075RE, ADS076RE, ADS067RE, and ADS077RE.

[0065] Exemplary QD materials include, but are not limited to, group II-IV compound semiconductors such as CdS, CdSe, CdS/ZnS, CdSe/ZnS or CdSe/CdS/ZnS, group II-VI, such as CdTe, ZnSe, ZnTe, ZnS, HgTe, HgS, HgSe, CdSeTe, CdSTe, ZnSeS, ZnSeTe, ZnSTe, HgSeS, HgSeTe, HgSTe, CdZnS, CdZnSe, CdZnTe, CdHgS, CdHgSe, CdHgTe, HgZnS, HgZnSe, HgZnTe, CdZnSeS, CdZnSeTe, CdZnSTe, CdHgSeS, CdHgSeTe, CdHgSTe, HgZnSeS, HgZnSeTe, HgZnSTe, group III-V or group IV-VI compound semiconductors such as GaN, GaP, GaNP, GaNAs, GaPAs, GaAs, GaAlNP, GaAlNAs, GaAlPAs, GaInNP, GaInNAs, GaInPAs, AlN, AlNP, AlNAs, AlP, AlPAS, AlAs, InN, InNP, InP, InNAs, InPAs, InAS, InAlNP, InAlNAs, InAlPAs, PbS/ZnS or PbSe/ZnS, group IV, such as Si, Ge, SiC, and SiGe, chalcopyrite-type compounds, including, but not limited to, CuInS.sub.2, CuInSe.sub.2, CuGaS.sub.2, CuGaSe.sub.2,

AgInS.sub.2, AgInSe.sub.2, AgGaS.sub.2, AgGaSe.sub.2 or perovskite QDs having a formula of ABX.sub.3 where A is cesium, methylammonium or formamidinium, B is lead or tin and C is chloride, bromide or iodide.

[0066] In one embodiment, the perovskite quantum dot may be CsPbX₃, where X is Cl, Br, I or a combination thereof. The mean size of the QD materials may range from about 2 nm to about 20 nm. The surface of QD particles may be further modified with ligands such as amine ligands, phosphine ligands, phosphatide and polyvinylpyridine. In one aspect, the red phosphor may be a quantum dot material.

[0067] All of the semiconductor quantum dots may also have appropriate shells or coatings for passivation and/or environmental protection. The QD materials may be a core/shell QD, including a core, at least one shell coated on the core, and an outer coating including one or more ligands, preferably organic polymeric ligands. Exemplary materials for preparing core-shell QDs include, but are not limited to, Si, Ge, Sn, Se, Te, B, C (including diamond), P, Co, Au, BN, BP, BAS, AlN, AlP, AlAs, AlSb, GaN, GaP, GaAs, GaSb, InN, InP, InAs, InSb, AlN, AlP, AlAs, AlSb, GaN, GaP, GaAs, GaSb, ZnO, ZnS, ZnSe, ZnTe, CdS, CdSe, CdSeZn, CdTe, HgS, HgSe, HgTe, BeS, BeSe, BeTe, MgS, MgSe, MnS, MnSe, GeS, GeSe, GeTe, SnS, SnSe, SnTe, PbO, PbS, PbSe, PbTe, CuF, CuCl, CuBr, CuI, Si.sub.3N.sub.4, Ge.sub.3N.sub.4, Al.sub.2O.sub.3, [Al, Ga, In].sub.2 [S, Se, Te].sub.3, and appropriate combinations of two or more such materials. Exemplary core-shell luminescent nanocrystals include, but are not limited to, CdSe/ZnS, CdSe/CdS, CdSe/CdS/ZnS, CdSeZn/CdS/ZnS, CdSeZn/ZnS, InP/ZnS, PbSe/PbS, PbSe/PbS, CdTe/CdS and CdTe/ZnS.

[0068] In one embodiment, the phosphor composition may include scattering particles. In one embodiment, the scattering particles have a particle size of at least 1 μm. In another embodiment, the scattering particles have a particle size from about 1 μm to about 10 μm. In another embodiment, the scattering particles may include titanium dioxide, aluminum oxide (Al.sub.2O.sub.3), zirconium oxide, indium tin oxide, cerium oxide, tantalum oxide, zinc oxide, magnesium fluoride (MgF.sub.2), calcium fluoride (CaF.sub.2), strontium fluoride (SrF.sub.2), barium fluoride (BaF.sub.2), silver fluoride (AgF), aluminum fluoride (AlF.sub.3) or combinations thereof.

[0069] The ratio of each of the individual phosphors and other luminescent materials in the phosphor composition may vary depending on the characteristics of the desired light output. The relative proportions of the individual phosphors and other luminescent materials in the various phosphor compositions may be adjusted such that when their emissions are blended and employed in a device, for example a lighting apparatus, there is produced visible light of predetermined x and y values on the CIE chromaticity diagram.

[0070] The phosphor composition may be in the form of an ink or slurry composition, which can be applied to a substrate, such as an LED light source or formed into a film. The ink composition may be blended with a binder or a solvent.

[0071] Examples of binders include, but are not limited to silicone polymers, polysiloxanes, ethyl cellulose, polystyrene, polyacrylate, polymethyl acrylate (PMA), polymethyl methacrylate (PMMA), polycarbonate, polyurethane, polyetherether ketone, polysulfone, polyphenylene sulfide, polyvinylpyrrolidone (PVP), polyethyleneimine (PEI), poly(1-naphthyl methacrylate), poly(vinyl phenyl sulfide) (PVPS), polyvinyl alcohol (PVA), polyvinyl butyral (PVB), poly(N-vinylphthalimide), polyvinylidene fluoride (PDVF), poly(vinylidene fluoride-co-hexafluoropropylene) (PVDF-HFP), silicone materials and UV-curable materials, such as epoxy resins, acrylic resins, acrylate resins and urethane-based materials.

[0072] Examples of solvents include, but are not limited to, water, ethanol, acetone and isopropanol.

[0073] In another aspect, a device includes an LED light source optically coupled and/or radiationally connected to a phosphor composition, wherein the phosphor composition includes a red phosphor material having a red decay rate and a green phosphor material having a green decay

rate, wherein the red phosphor material includes a Mn.sup.4+ doped phosphor of formula I and a Eu.sup.3+ doped uranium phosphor, and wherein a difference between the red decay rate and the green decay rate is no more than 7 ms,

A.sub.xMF.sub.y:Mn.sup.4+ (I),

wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7.

[0074] In one embodiment, a lighting apparatus includes the device. In another embodiment, a backlight apparatus includes the device. In another embodiment, a display includes the device. In another embodiment, the device is a self-emissive display and does not contain a liquid crystal display (LCD). In one embodiment, the display is a micro-LED display, such as a phosphor-converted microLED display.

[0075] Devices according to the present disclosure include an LED light source radiationally connected and/or optically coupled to the phosphor composition. FIG. 1 shows a device **10**, according to one embodiment of the present disclosure. The device **10** includes an LED light source **12** and the phosphor composition **14**. The LED light source **12** may be a UV or blue emitting LED. In some embodiments, the LED light source **12** produces blue light in a wavelength range from about 380 nm to about 460 nm. In the device **10**, the phosphor composition **14** is radiationally coupled and/or optically coupled to the LED light source **12**. Radiationally connected or coupled or optically coupled means that radiation from the LED light source **12** is able to excite the phosphor composition **14**, and the phosphor composition **14** is able to emit light in response to the excitation by the radiation. The phosphor composition **14** may be disposed on a part or portion of the LED light source **12** or located remotely at a distance from the LED light source **12**. In some embodiments, the device may be a backlight unit for display applications. In other embodiments, the LED light source **12** is a micro-LED and the device is for a self-emissive display.

[0076] The general discussion of the example LED light source discussed herein is directed toward an inorganic LED based light source. The most popular white LEDs are based on blue or UV emitting GaInN chips. In addition, to inorganic LED light sources, the term LED light source is meant to encompass all LED light sources such as semiconductor laser diodes (LD), organic light emitting diodes (OLED) or a hybrid of LED and LD. The LED light source may be a miniLED or microLED, which can be used in self-emissive displays. Further, it should be understood that the LED light source may be replaced, supplemented or augmented by another radiation source unless otherwise noted and that any reference to semiconductor, semiconductor LED, or LED chip is merely representative of any appropriate radiation source, including, but not limited to, LDs and OLEDs.

[0077] The phosphor composition **14** may be present in any form such as powder, glass, or composite e.g., phosphor-polymer composite or phosphor-glass composite. Further, the phosphor composition **14** may be used as a layer, sheet, film, strip, dispersed particulates, or a combination thereof. In some embodiments, the phosphor composition **14** includes the uranium-based phosphor material in glass form. In some of these embodiments, the device **10** may include the phosphor composition **14** in form of a phosphor wheel (not shown). The phosphor wheel may include the phosphor composition embedded in a glass. A phosphor wheel and related devices are described in WO 2017/196779.

[0078] The phosphor composition is optically coupled or radiationally connected to an LED light source. In one embodiment, a white light blend may be obtained by blending the red phosphor material and the green phosphor material with an LED light source, such as a blue or UV LED.

[0079] FIG. 2 illustrates a lighting apparatus or lamp **20**, in accordance with some embodiments. In one embodiment, the lighting apparatus **20** may be a backlight apparatus. The lighting apparatus **20** includes an LED chip **22** and leads **24** electrically attached to the LED chip **22**. The leads **24** may

comprise thin wires supported by a thicker lead frame(s) **26** or the leads **24** may comprise self-supported electrodes and the lead frame may be omitted. The leads **24** provide current to LED chip **22** and thus cause it to emit radiation.

[0080] A layer **30** of the phosphor composition is disposed on a surface of the LED chip **22**. The phosphor layer **30** may be disposed by any appropriate method, for example, using a slurry or ink composition prepared by mixing the phosphor composition and a binder material or solvent (as discussed above). In one such method, a silicone slurry in which the phosphor composition particles are randomly suspended or uniformly dispersed is placed around the LED chip **22**. This method is merely exemplary of possible positions of the phosphor layer **30** and LED chip **22**. The phosphor layer **30** may be coated over or directly on the light emitting surface of the LED chip **22** by coating and drying the slurry over the LED chip **22**. The light emitted by the LED chip **22** mixes with the light emitted by the phosphor composition to produce desired emission.

[0081] With continued reference to FIG. **2**, the LED chip **22** may be encapsulated within an envelope **28**. The envelope **28** may be formed of, for example glass or plastic. The LED chip **22** may be enclosed by an encapsulant material **32**. The encapsulant material **32** may be a low temperature glass, or a polymer or resin known in the art, for example, an epoxy, silicone, epoxy-silicone, acrylate or a combination thereof. In an alternative embodiment, the lighting apparatus **20** may only include the encapsulant material **32** without the envelope **28**. Both the envelope **28** and the encapsulant material **32** should be transparent to allow light to be transmitted through those elements.

[0082] In some embodiments as illustrated in FIG. **3**, the phosphor composition **33** is interspersed within the encapsulant material **32**, instead of being formed directly on the LED chip **22**, as shown in FIG. **2**. The phosphor composition **33** may be interspersed within a portion of the encapsulant material **32** or throughout the entire volume of the encapsulant material **32**. Blue light or UV light emitted by the LED chip **22** mixes with the light emitted by phosphor composition **33**, and the mixed light transmits out from the lighting apparatus **20**.

[0083] In yet another embodiment, a layer **34** of the phosphor composition is coated onto a surface of the envelope **28**, instead of being formed over the LED chip **22**, as illustrated in FIG. **4**. As shown, the phosphor layer **34** is coated on an inside surface **29** of the envelope **28**, although the phosphor layer **34** may be coated on an outside surface of the envelope **28**, if desired. The phosphor layer **34** may be coated on the entire surface of the envelope **28** or only a top portion of the inside surface **29** of the envelope **28**. The UV/blue light emitted by the LED chip **22** mixes with the light emitted by the phosphor layer **34**, and the mixed light transmits out. Of course, the phosphor composition may be located in any two or all three locations (as shown in FIGS. **2-4**) or in any other suitable location, such as separately from the envelope **28**, remote or integrated into the LED chip **22**. In one embodiment, the phosphor layer **34** may be a film and located remotely from the LED chip **22**. In another embodiment, the phosphor layer **34** may be a film and disposed on the LED chip **22**. In some embodiments, the phosphor layer **34** may be applied to the LED chip **22** as an ink composition. In some embodiments, the phosphor layer **34** may be applied to the LED chip **22** as an ink composition and dried to form a film on the LED chip **22**. In some embodiments, the phosphor composition may be a single layer or multi-layered. In some embodiments, the film is a multi-layered structure where each layer of the multi-layered structure includes at least one phosphor or quantum dot material. In another embodiment, a device structure includes a layer of a phosphor composition on an LED chip and a remote layer including a quantum dot material. In another embodiment, a device structure includes a layer of a phosphor composition on an LED chip and a remote layer including a quantum dot material and phosphor material. In another embodiment, a device structure includes a layer of a phosphor composition on an LED chip and a film including quantum dot material located remotely from the LED chip. In another embodiment, a device structure includes a layer of a phosphor composition on an LED chip and a film including quantum dot material and phosphor material located remotely from the LED chip.

[0084] In any of the above structures, the lighting apparatus 20 (FIGS. 2-4) may also include a plurality of scattering particles (not shown), which are embedded in the encapsulant material 32. The scattering particles may comprise, for example, alumina, silica, zirconia, or titania. The scattering particles effectively scatter the directional light emitted from the LED chip 22, preferably with a negligible amount of absorption.

[0085] In one embodiment, the lighting apparatus 20 shown in FIG. 3 or FIG. 4 may be a backlight apparatus. In another embodiment, the backlight apparatus comprises a backlight unit 10. Some embodiments include a surface mounted device (SMD) type light emitting diode 50, e.g. as illustrated in FIG. 5, for backlight applications. This SMD is a “side-emitting type” and has a light-emitting window 52 on a protruding portion of a light guiding member 54. An SMD package may comprise an LED chip as defined above, and a phosphor composition including the green-emitting phosphor as described herein. In another embodiment, the device may be a direct lit display.

[0086] By use of the phosphor compositions described herein, devices can be provided producing white light for display applications, for example, LCD backlight units, having high color gamut and high luminosity. Alternately, devices can be provided producing white light for general illumination having high luminosity and high CRI values for a wide range of color temperatures of interest (2000 K to 10,000 K).

[0087] Devices of the present disclosure include lighting and display apparatuses for general illumination and display applications. Examples of display apparatuses include liquid crystal display (LCD) backlight units, televisions, computer monitors, vehicular displays, laptops, computer notebooks, mobile phones, smartphones, tablet computers and other handheld devices. Where the display is a backlight unit, the phosphor composition may be incorporated in a film, sheet or strip that is radiationally coupled and/or optically coupled to the LED light source, as described in US Patent Application Publication No. 2017/0254943. Examples of other devices include chromatic lamps, plasma screens, xenon excitation lamps, UV excitation marking systems, automotive headlamps, home and theatre projectors, laser pumped devices, and point sensors. In one embodiment, the device may be a fast response display that does not include an LCD. The fast response display may be a self-emissive display including phosphor converted (PC) micro-LEDs. The list of these applications is meant to be merely exemplary and not exhaustive.

[0088] In some embodiments, films including the phosphor composition may be disposed on small-size LEDs, such as micro-LEDs or mini-LEDs. In other embodiments, the film includes phosphor particle sizes from about 0.1 to about 15 microns. In other embodiments, of no more than 5 microns. In another embodiment, the film includes phosphor particles sizes of from about 0.1 micron to about 5 microns. In another embodiment, the film includes particle sizes of from about 0.5 micron to about 5 microns. In another embodiment, the film includes particle sizes from about 0.1 micron to about 1 micron. In another embodiment, the film includes particle sizes from about 0.5 micron to about 1 micron. In another embodiment, the film includes particle sizes from about 1 micron to about 3 microns.

[0089] Although specific features of various embodiments of the disclosure may be shown in some drawings and not in others, this is for convenience only. In accordance with the principles of the disclosure, any feature of a drawing may be referenced and/or claimed in combination with any feature of any other drawing.

EXAMPLES

Example 1

Preparation of Eu.SUP.3+ doped uranium phosphor Na.SUB.2.UO.SUB.2.P.SUB.2.O.SUB.7 .doped with 1% molar amount of Eu.SUP.3+ (Sample DU-Red)

[0090] Na.sub.2CO.sub.3, H2O.sub.2PO.sub.4·4H.sub.2O, NaH.sub.2PO.sub.4 and Eu.sub.2O.sub.3 were weighted out in a mol ratio of 0.495:1:1:0.005 and then put in a Nalgene bottle with zirconia media and ball milled for two hours. After the mixture was thoroughly blended the powder was transferred into an alumina crucible and fired at 500° C. for 5 hours, the mixture

was then sieved through a 40-mesh screen and blended again in the same Nalgene bottle for two additional hours. The powder was put back into the alumina crucible and fired at 900° C. for 5 hours. After the final firing the phosphor powder was obtained. The ccx and ccy values, decay time and refresh rate for Na.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+ (DU-Red) are shown in Tables 1 and 2.

Preparation of BaZnUO.SUB.2.(PO.SUB.4.).SUB.2.(Sample Green A)

[0091] BaHPO.sub.4, HUO.sub.2PO.sub.4—4H.sub.2O, ZnO and DAP were weighed out in a mol ratio of 1:1:1:0.05 and then put in a Nalgene bottle with zirconia media and ball milled for two hours. After the mixture was thoroughly blended the powder was transferred into an alumina crucible and fired at 1050° C. for 5 hours under flowing wet air. After firing, a yellow body-colored powder was obtained. The ccx and ccy values, decay time and refresh rate for BaZnUO.sub.2(PO.sub.4).sub.2(Green A) are shown in Tables 1 and 2.

Preparation of gamma-Ba.SUB.2.UO.SUB.2.(PO.SUB.4.).SUB.2.(Sample Green B)

[0092] For preparing gamma-Ba.sub.2UO.sub.2(PO.sub.4).sub.2, BaHPO.sub.4, UO.sub.2, and DAP were weighed out in a mol ratio of 2:1:0.05 and then put in a Nalgene bottle with zirconia media and ball milled for two hours. After the mixture was thoroughly blended the powder was transferred into an alumina crucible and fired at 1100° C. for 5 hours in air. After firing a yellow body colored powder was obtained. The cox and ccy values, decay time and refresh rate for gamma-Ba.sub.2UO.sub.2(PO.sub.4).sub.2(Green B) are shown in Tables 1 and 2. The XRD powder pattern for gamma-Ba.sub.2UO.sub.2(PO.sub.4).sub.2 is shown in FIG. 6.

TABLE-US-00001 TABLE 1 Sample or ccx ccy Compound (Edinburgh) (Edinburgh) DU-Red 0.6568 0.3429 NSF 0.6863 0.3136 Green A 0.2187 0.6698 Green B 0.2785 0.6731 LED 0.1529 0.0255 (from calculator) (from calculator) PFS 0.6938 0.3060 (from calculator) (from calculator) Beta-SiAlON 0.3460 0.6307 (from calculator) (from calculator)

TABLE-US-00002 TABLE 2 Decay Refresh Refresh Refresh Sample (ms) Hz Rate (s) Rate (ms) Rate (μs) DU-Red 1.8 120 0.008333333 8.33333333 8333.333 NSF 6 240 0.004166667 4.166666667 4166.667 Green A 0.52 60 0.016666667 16.66666667 16666.67 Green B 0.09

[0093] The red phosphor material was prepared by blending the DU-Red sample and the NSF sample in different amounts as shown in Table 3. Quantum efficiency measurements of the red phosphor material were performed on cured silicone tape. Phosphor particles were dispersed in a 2-part thermally curable polydimethylsiloxane elastomer (such as is sold as Sylgard® 184 from Dow Corning) by mixing. The dispersed phosphor particles were prepared at a concentration of 0.17 g of phosphor to 1.8 g of silicone. The mixture was applied to a silicone tape and cured. The quantum efficiencies (QE) of the phosphor particles were measured in these films. The LED was a blue LED with a ccx of 0.1529 and ccy of 0.0205. The QE measurements were reported in relation to the QE of potassium fluoride sulfide phosphors (PFS). The Bleedthrough value is the amount of blue coming through the tape. Data for the red phosphor material is in Table 3 and the emission spectrum for the DU-Red sample and the NFS sample is shown in FIG. 7 and the emission spectrum showing the combination of the DU-Red and NFS samples is in FIG. 8.

TABLE-US-00003 TABLE 3 Peak Peak DU- NSF DU- ccx ccy Ratio ratio Red Wt. Red NSF Bleed- with with for for Wt. % % Vol. % Vol. % QE through ccx ccy LED LED 618 627 100 0 100 0 0.948 0.405 0.6582 0.3415 0.3461 0.1513 100 0 75 25 65.5 34.5 0.950 0.458 0.6606 0.3391 0.3208 0.1331 89.5 10.5 50 50 38.8 61.2 0.950 0.501 0.6641 0.3356 0.3027 0.1192 82 18 25 75 17.4 82.6 0.968 0.593 0.6704 0.3294 0.2670 0.0938 68 32

[0094] The decay times for the red phosphor material for the amounts shown in Table 3 and FIG. 8 are shown in Table 4. The red decay rates for the red phosphor material are reduced in comparison with NSF alone. The red phosphor material maintains a good quantum efficiency and large color gamut.

TABLE-US-00004 TABLE 4 DU-Red NSF Red Decay Decay Decay DU-Red NSF Rate Rate Rate Wt. % Wt. % (ms) (ms) (ms) 100 0 1.8 1.8 75 25 1.8 6 2.85 50 50 1.8 6 3.9 25 75 1.8 6 4.95

TABLE-US-00005 TABLE 5 Mismatch or Mismatch or Green A Green B difference difference
 Red Decay Decay between Red between Red Decay Rate Rate and Green A and Green B Rate (ms)
 (ms) (ms) (ms) 2.85 0.52 0.09 2.33 2.76 3.9 0.52 0.09 3.38 3.81 4.95 0.52 0.09 4.43 4.86

[0095] The difference in the decay rates between the red phosphor material at 50 wt % and the green phosphor material at 50 wt % is shown in Table 5. The difference in the decay rates between the red phosphor material and Green A and the difference in the decay rates between the red phosphor material and Green B are all below 7, which reduces display lag and blurring.

[0096] This written description uses examples to disclose the invention, including the best mode, and also to enable any person skilled in the art to practice the invention, including making and using any devices or systems and performing any incorporated methods. The patentable scope of the invention is defined by the claims, and may include other examples that occur to those skilled in the art. Such other examples are intended to be within the scope of the claims if they have structural elements that do not differ from the literal language of the claims, or if they include equivalent structural elements with insubstantial differences from the literal languages of the claims.

Claims

1. A phosphor composition comprises a red phosphor material having a red decay rate and a green phosphor material having a green decay rate, wherein the red phosphor material comprises a Mn.sup.4+ doped phosphor of formula I

A.sub.xMF.sub.y:Mn.sup.4+ (I), and a Eu.sup.3+ doped uranium phosphor, wherein a difference between the red decay rate and the green decay rate is no more than 7 ms, and wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7.

2. The phosphor composition according to claim 1, wherein the Mn.sup.4+ doped phosphor is selected from the group consisting of: K.sub.2(SiF.sub.6):Mn.sup.4+, K.sub.2(TiF.sub.6):Mn.sup.4+, K.sub.2(SnF.sub.6):Mn.sup.4+, Cs.sub.2(TiF.sub.6):Mn.sup.4+, Rb.sub.2(TiF.sub.6):Mn.sup.4+, Cs.sub.2(SiF.sub.6):Mn.sup.4+, Rb.sub.2(SiF.sub.6):Mn.sup.4+, Na.sub.2(TiF.sub.6):Mn.sup.4+, Na.sub.2(SiF.sub.6):Mn.sup.4+, Na.sub.2(ZrF.sub.6):Mn.sup.4+, K.sub.3(ZrF.sub.7):Mn.sup.4+, K.sub.3(BiF.sub.7):Mn.sup.4+, K.sub.3(YF.sub.7):Mn.sup.4+, K.sub.3(LaF.sub.7):Mn.sup.4+, K.sub.3(GdF.sub.7):Mn.sup.4+, K.sub.3(NbF.sub.7):Mn.sup.4+, and K.sub.3(TaF.sub.7):Mn.sup.4+.

3. The phosphor composition according to claim 1, wherein the Mn.sup.4+ doped phosphor has a Mn loading or Mn % of at least 1 wt %.

4. (canceled)

5. The phosphor composition according to claim 1, wherein the Mn.sup.4+ doped phosphor comprises a surface coating, and the surface coating comprises a metal fluoride, wherein the metal fluoride is selected from the group consisting of MgF.sub.2, CaF.sub.2, SrF.sub.2, BaF.sub.2, AgF, ZnF.sub.2, AlF.sub.3 and a combination thereof.

6. (canceled)

7. The phosphor composition according to claim 1, wherein the Eu.sup.3+ doped uranium phosphor is selected from the group consisting of: (i) a Eu.sup.3+ doped uranium phosphor having formula IIA

[Ba.sub.1-a-

bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3:Eu.sup.3+ (IIA) wherein 0≤a≤1, 0≤b≤1, 0.75≤x≤1.25, 0.75≤y≤1.25, 0.75≤z≤1.25; (ii) a Eu.sup.3+ doped uranium phosphor having formula IIB

[Ba.sub.1-a-

bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3:Eu.sup.3+ and A (IIB) wherein $0 \leq a \leq 1$, $0 \leq b \leq 1$, $0.75 \leq x \leq 1.25$, $0.75 \leq y \leq 1.25$, $0.75 \leq z \leq 1.25$ and A is Li.sup.+, Na.sup.+, K.sup.+, Rb.sup.+, Cs.sup.+, or mixtures thereof; (iii) a Eu.sup.3+ doped uranium phosphor having formula IIIA

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.(2p+2q+5r)/2:Eu.sup.3+ (IIIA) wherein $0 \leq a \leq 1$, $0 \leq b \leq 1$, $2.5 \leq p < 3.5$, $1.75 \leq q \leq 2.25$, $3.5 \leq r \leq 4.5$; (iv) a Eu.sup.3+ doped uranium phosphor having formula IIIB

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.(2p+2q+5r)/2:Eu.sup.3+ and A (IIIB) wherein $0 \leq a \leq 1$, $0 \leq b \leq 1$, $2.5 \leq p \leq 3.5$, $1.75 \leq q \leq 2.25$, $3.5 \leq r \leq 4.5$ and A is Li.sup.+, Na.sup.+, K.sup.+, Rb.sup.+, Cs.sup.+, or mixtures thereof; and (v) a Eu.sup.3+ doped uranium phosphor having formula IV

A.sub.2UO.sub.2[P,V].sub.2O.sub.7:Eu.sup.3+ (IV) wherein A is Li, Na, K, Rb, Cs, or a combination thereof.

8. The phosphor composition according to claim 1, wherein the Eu.sup.3+ doped uranium phosphor is selected from the group consisting of: BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+;

BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and

Li.sup.+; BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Na.sup.+;

BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and K.sup.+;

BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Rb.sup.+;

BaMgUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Cs.sup.+;

BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Li.sup.+;

BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Na.sup.+;

BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and K.sup.+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and

Rb.sup.+; BaZnUO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Cs.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Li.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Na.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and

K.sup.+Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Rb.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7:Eu.sup.3+ and Cs.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Li.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Na.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and K.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Rb.sup.+;

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7:Eu.sup.3+ and Cs.sup.+; γ-

Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+; γ-Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and

Li.sup.+; γ-Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Na.sup.+; γ-

Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and K.sup.+; γ-

Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Rb.sup.+; and γ-

Ba.sub.2UO.sub.2(PO.sub.4).sub.2:Eu.sup.3+ and Cs.sup.+;

Na.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+, K.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+ and mixtures thereof.

9. The phosphor composition according to claim 1, wherein the red phosphor material comprises

Na.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+ and either Na.sub.2SiF.sub.6:Mn.sup.4+ or

K.sub.2SiF.sub.6:Mn.sup.4+.

10. The phosphor composition according to claim 1, wherein the green phosphor material

comprises a green-emitting phosphor selected from the group consisting of: (i) a green-emitting phosphor having formula V

[Ba.sub.1-a-

bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V]O.sub.4).sub.2(x+y+z)/3 (V); (ii) a green-emitting phosphor having formula VI

$$[\text{Ba.sub.1-a-bSr.sub.aCa.sub.b}].\text{sub.p}(\text{UO.sub.2}).\text{sub.q}[\text{P,V}].\text{sub.rO.sub.}(2\text{p}+2\text{q}+5\text{r})/2$$
 (VI); (iii) a green-emitting phosphor having formula VII

$$\text{A.sub.2UO.sub.2}[\text{P,V}].\text{sub.2O.sub.7}$$
 (VII); (iv) a green-emitting phosphor having formula VIII

$$\text{A.sub.4UO.sub.2}([\text{P,V}]\text{O.sub.4}).\text{sub.2}$$
 (VIII); and (v) a green-emitting phosphor having formula IX

$$\text{AUO.sub.2}([\text{P,V}]\text{O.sub.3}).\text{sub.3}$$
 (IX) wherein $0 \leq a \leq 1$, $0 \leq b \leq 1$, $0.75 \leq x \leq 1.25$, $0.75 \leq y \leq 1.25$, $0.75 \leq z \leq 1.25$; $2.5 \leq p \leq 3.5$, $1.75 \leq q \leq 2.25$, $3.5 \leq r \leq 4.5$ and A is Li, Na, K, Rb, Cs, or a combination thereof.

11. The phosphor composition according to claim 1, wherein the green phosphor material comprises a green-emitting phosphor selected from the group consisting of:

Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2P.sub.2O.sub.7,
Ba.sub.3(PO.sub.4).sub.2(UO.sub.2).sub.2V.sub.2O.sub.7, gamma γ-
Ba.sub.2UO.sub.2(PO.sub.4).sub.2, BaMgUO.sub.2(PO.sub.4).sub.2,
BaZnUO.sub.2(PO.sub.4).sub.2, Na.sub.2UO.sub.2P.sub.2O.sub.7,
K.sub.2UO.sub.2P.sub.2O.sub.7, Rb.sub.2UO.sub.2P.sub.2O.sub.7,
Cs.sub.2UO.sub.2P.sub.2O.sub.7, K.sub.4UO.sub.2(PO.sub.4).sub.2,
K.sub.4UO.sub.2(VO.sub.4).sub.2, NaUO.sub.2P.sub.3O.sub.9, and combinations thereof.

12. The phosphor composition according to claim 1, wherein the red phosphor material comprises Na.sub.2UO.sub.2P.sub.2O.sub.7:Eu.sup.3+ and either K.sub.2SiF.sub.6:Mn.sup.4+ or Na.sub.2SiF.sub.6:Mn.sup.4+ and the green phosphor material comprises BaZnUO.sub.2(PO.sub.4).sub.2 or γ-Ba.sub.2UO.sub.2(PO.sub.4).sub.2.

13. The phosphor composition according to claim 1 further comprising one or more other luminescent materials.

14. The phosphor composition according to claim 13, wherein the one or more other luminescent material comprises an additional phosphor selected from the group consisting of:

[Y,Gd,Lu,Tb].sub.3[Al,Ga].sub.5O.sub.12:Ce.sup.3+, β-SiAlON:Eu.sup.2+, [Sr,Ca,Ba]
[Ga,Al].sub.2S.sub.4:Eu.sup.2+, [Li,Ca]α-SiAlON:Eu.sup.2+,
[Ba,Sr,Ca].sub.2Si.sub.5N.sub.8:Eu.sup.2+, [Ca,Sr] AlSiN.sub.3:Eu.sup.2+,
[Ba,Sr,Ca]LiAl.sub.3N.sub.4:Eu.sup.2+, [Sr,Ca,Mg]S:Eu.sup.2+, and
[Ba,Sr,Ca].sub.2Si.sub.2O.sub.4:Eu.sup.2+.

15. The phosphor composition according to claim 13, wherein the one or more other luminescent material comprises at least one of electroluminescent polymers, phosphorescent dye, a quantum dot material, or scattering particles.

16-18. (canceled)

19. The phosphor composition according to claim 10, wherein the Mn.sup.4+ doped phosphor, the Eu.sup.3+ doped uranium phosphor and the green-emitting phosphor are in particulate form comprising a monodisperse population of particles having a particle size distribution comprising a D50 particle size from about 0.1 μm to about 15 μm.

20. A device comprising an LED light source optically coupled and/or radiationally connected to a phosphor composition, wherein the phosphor composition includes a red phosphor material having a red decay rate and a green phosphor material having a green decay rate, wherein the red phosphor material includes a Mn.sup.4+ doped phosphor of formula I,

$$\text{A.sub.xMF.sub.y:Mn.sup.4+}$$
 (I), and a Eu.sup.3+ doped uranium phosphor, wherein a difference between the red decay rate and the green decay rate is no more than 7 ms, and wherein A is Li, Na, K, Rb, Cs, or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; x is an absolute value of a charge of the MF.sub.y ion; and y is 5, 6 or 7.

21. (canceled)

22. The device according to claim 20, wherein the Mn.sup.4+ doped phosphor is selected from the group consisting of: K.sub.2(SiF.sub.6):Mn.sup.4+, K.sub.2(TiF.sub.6):Mn.sup.4+, K.sub.2(SnF.sub.6):Mn.sup.4+, Cs.sub.2(TiF.sub.6):Mn.sup.4+, Rb.sub.2(TiF.sub.6):Mn.sup.4+, Cs.sub.2(SiF.sub.6):Mn.sup.4+, Rb.sub.2(SiF.sub.6):Mn.sup.4+, Na.sub.2(TiF.sub.6):Mn.sup.4+, Na.sub.2(SiF.sub.6):Mn.sup.4+, Na.sub.2(ZrF.sub.6):Mn.sup.4+, K.sub.3(ZrF.sub.7):Mn.sup.4+, K.sub.3(BiF.sub.7):Mn.sup.4+, K.sub.3(YF.sub.7):Mn.sup.4+, K.sub.3(LaF.sub.7):Mn.sup.4+, K.sub.3(GdF.sub.7):Mn.sup.4+, K.sub.3(NbF.sub.7):Mn.sup.4+, and K.sub.3(TaF.sub.7):Mn.sup.4+ and the Eu.sup.3+ doped uranium phosphor is selected from the group consisting of: (i) a Eu.sup.3+ doped uranium phosphor having formula IIA

[Ba.sub.1-a-

bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3:Eu.sup.3+ (IIA) wherein 0≤a≤1, 0≤b≤1, 0.75≤x≤1.25, 0.75≤y≤1.25, 0.75≤z≤1.25; (ii) a Eu.sup.3+ doped uranium phosphor having formula IIB

[Ba.sub.1-a-

bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3:Eu.sup.3+ and A (IIB) wherein 0≤a≤1, 0≤b≤1, 0.75≤x≤1.25, 0.75≤y≤1.25, 0.75≤z≤1.25 and A is Li.sup.+, Na.sup.+, K.sup.+, Rb.sup.+, Cs.sup.+, or mixtures thereof; (iii) a Eu.sup.3+ doped uranium phosphor having formula IIIA

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.

(2p+2q+5r)/2:Eu.sup.3+ (IIIA) wherein 0≤a≤1, 0≤b≤1.25, 2.5≤p≤3.5, 1.75≤q≤2.25, 3.5≤r≤4.5; and (iv) a Eu.sup.3+ doped uranium phosphor having formula IIIB

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.(2p+2q+5r)/2:Eu.sup.3+ and A (IIIB) wherein 0≤a≤1, 0≤b≤1, 2.5≤p≤3.5, 1.75≤q≤2.25, 3.5≤r≤4.5 and A is Li.sup.+, Na.sup.+, K.sup.+, Rb.sup.+, Cs.sup.+, or mixtures thereof; and (v) a Eu.sup.3+ doped uranium phosphor having formula IV

A.sub.2UO.sub.2[P,V].sub.2O.sub.7:Eu.sup.3+ (IV) wherein A is Li, Na, K, Rb, Cs, or a combination thereof.

23-25. (canceled)

26. The device according to claim 20, wherein the green phosphor material comprises a green-emitting phosphor selected from the group consisting of: (i) a green-emitting phosphor having formula V

[Ba.sub.1-a-

bSr.sub.aCa.sub.b].sub.x[Mg,Zn].sub.y(UO.sub.2).sub.z([P,V])O.sub.4).sub.2(x+y+z)/3 (V); (ii) a green-emitting phosphor having formula VI

[Ba.sub.1-a-bSr.sub.aCa.sub.b].sub.p(UO.sub.2).sub.q[P,V].sub.rO.sub.(2p+2q+5r)/2 (VI); (iii) a green-emitting phosphor having formula VII

A.sub.2UO.sub.2[P,V].sub.2O.sub.7 (VII); (iv) a green-emitting phosphor having formula VIII

A.sub.4UO.sub.2([P,V])O.sub.4).sub.2 (VIII); and (v) a green-emitting phosphor having formula IX

AUO.sub.2([P,V])O.sub.3).sub.3 (IX) wherein 0≤a≤1, 0≤b≤1, 0.75≤x≤1.25, 0.75≤y≤1.25, 0.75≤z≤1.25; 2.5≤p≤3.5, 1.75≤q≤2.25, 3.5≤r≤4.5 and A is Li, Na, K, Rb, Cs, or a combination thereof.

27-30. (canceled)

31. The device according to claim 20, wherein the phosphor composition is in a form of a film and is located remotely from the LED light source.

32. (canceled)

33. A lighting apparatus, a backlight apparatus, a display apparatus, or a self-emissive display comprising the device of claim 20.

34-36. (canceled)

37. The device according to claim 20, wherein the device is a television, a mobile phone, a computer monitor, a laptop, a tablet, or an automotive display.

38-45. (canceled)
