

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250284041

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

SINGH; Vikramjit et al.

ULTRASONICATION NANO-GEOMETRY CONTROL PROCESS AND METHODS

Abstract

Disclosed herein are systems and methods for fabricating nanostructures on a substrate that can be used in eyepieces for displays, e.g., in head wearable devices. Fabricating and/or etching such a substrate can include submerging the substrate in a bath and applying ultrasonication to the bath for a first time period. The ultrasonication applied to the first bath can agitate the fluid to provide a substantially uniform first reactive environment across the surface of the substrate. The substrate can be submerged in a second bath and ultrasonication can be applied to the second bath for a second time period. The ultrasonication applied to the second bath can agitate the fluid to provide a substantially uniform second reactive environment across the surface of the substrate. A predetermined amount of material can be removed from the surface of the substrate during the second time period to produce an etched substrate.

Inventors: SINGH; Vikramjit (Pflugerville, TX), MCDONALD; Lorenzo (Pflugerville, TX), XU; Frank Y. (Austin, TX)

Applicant: Magic Leap, Inc. (Plantation, FL)

Family ID: 83723259

Appl. No.: 18/555445

Filed (or PCT Filed): April 19, 2022

PCT No.: PCT/US2022/071803

Related U.S. Application Data

us-provisional-application US 63177294 20210420

Publication Classification

Int. Cl.: G02B5/18 (20060101); **B82Y20/00** (20110101); **B82Y40/00** (20110101); **G02B1/02** (20060101); **G02B25/00** (20060101); **G02B27/01** (20060101)

U.S. Cl.:

CPC G02B5/1857 (20130101); **B82Y20/00** (20130101); **B82Y40/00** (20130101); **G02B1/02** (20130101); **G02B5/1809** (20130101); **G02B5/1814** (20130101); **G02B25/001** (20130101); **G02B27/0172** (20130101); **G02B2027/0178** (20130101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This application claims priority to U.S. Provisional Application No. 63/177,294, filed on Apr. 20, 2021, the contents of which are incorporated by reference herein in its entirety.

FIELD

[0002] This disclosure relates in general to systems and methods for displaying visual information, and in particular to eyepieces for displaying visual information in an augmented reality or mixed reality environment. More specifically, this disclosure relates to systems and methods for fabricating gratings used in eyepieces for displaying visual information in an augmented reality or mixed reality environment.

BACKGROUND

[0003] Virtual environments are ubiquitous in computing environments, finding use in video games (in which a virtual environment may represent a game world); maps (in which a virtual environment may represent terrain to be navigated); simulations (in which a virtual environment may simulate a real environment); digital storytelling (in which virtual characters may interact with each other in a virtual environment); and many other applications. Modern computer users are generally comfortable perceiving, and interacting with, virtual environments. However, users' experiences with virtual environments can be limited by the technology for presenting virtual environments. For example, conventional displays (e.g., 2D display screens) and audio systems (e.g., fixed speakers) may be unable to realize a virtual environment in ways that create a compelling, realistic, and immersive experience.

[0004] Virtual reality ("VR"), augmented reality ("AR"), mixed reality ("MR"), and related technologies (collectively, "XR") share an ability to present, to a user of an XR system, sensory information corresponding to a virtual environment represented by data in a computer system. This disclosure contemplates a distinction between VR, AR, and MR systems (although some systems may be categorized as VR in one aspect (e.g., a visual aspect), and simultaneously categorized as AR or MR in another aspect (e.g., an audio aspect)). As used herein, VR systems present a virtual environment that replaces a user's real environment in at least one aspect; for example, a VR system could present the user with a view of the virtual environment while simultaneously obscuring his or her view of the real environment, such as with a light-blocking head-mounted display. Similarly, a VR system could present the user with audio corresponding to the virtual environment, while simultaneously blocking (attenuating) audio from the real environment.

[0005] VR systems may experience various drawbacks that result from replacing a user's real environment with a virtual environment. One drawback is a feeling of motion sickness that can arise when a user's field of view in a virtual environment no longer corresponds to the state of his or her inner ear, which detects one's balance and orientation in the real environment (not a virtual environment). Similarly, users may experience disorientation in VR environments where their own bodies and limbs (views of which users rely on to feel "grounded" in the real environment) are not

directly visible. Another drawback is the computational burden (e.g., storage, processing power) placed on VR systems, which must present a full 3D virtual environment, particularly in real-time applications that seek to immerse the user in the virtual environment. Similarly, such environments may need to reach a very high standard of realism to be considered immersive, as users tend to be sensitive to even minor imperfections in virtual environments-any of which can destroy a user's sense of immersion in the virtual environment. Further, another drawback of VR systems is that such applications of systems cannot take advantage of the wide range of sensory data in the real environment, such as the various sights and sounds that one experiences in the real world. A related drawback is that VR systems may struggle to create shared environments in which multiple users can interact, as users that share a physical space in the real environment may not be able to directly see or interact with each other in a virtual environment.

[0006] As used herein, AR systems present a virtual environment that overlaps or overlays the real environment in at least one aspect. For example, an AR system could present the user with a view of a virtual environment overlaid on the user's view of the real environment, such as with a transmissible head-mounted display that presents a displayed image while allowing light to pass through the display into the user's eye. Similarly, an AR system could present the user with audio corresponding to the virtual environment, while simultaneously mixing in audio from the real environment. Similarly, as used herein, MR systems present a virtual environment that overlaps or overlays the real environment in at least one aspect, as do AR systems, and may additionally allow that a virtual environment in an MR system may interact with the real environment in at least one aspect. For example, a virtual character in a virtual environment may toggle a light switch in the real environment, causing a corresponding light bulb in the real environment to turn on or off. As another example, the virtual character may react (such as with a facial expression) to audio signals in the real environment. By maintaining presentation of the real environment, AR and MR systems may avoid some of the aforementioned drawbacks of VR systems; for instance, motion sickness in users is reduced because visual cues from the real environment (including users' own bodies) can remain visible, and such systems need not present a user with a fully realized 3D environment in order to be immersive. Further, AR and MR systems can take advantage of real world sensory input (e.g., views and sounds of scenery, objects, and other users) to create new applications that augment that input.

[0007] Presenting a virtual environment in a realistic manner to create an immersive experience for the user in a robust and cost effective manner can be difficult. For example, a head mounted display can include an optical system having one or more multi-layered eyepieces, which can be an expensive and fragile component. For example, each layer may be manufactured via a complicated process that includes multiple steps to achieve diffractive gratings and associated films to effectively project a digital image to the user. The diffractive gratings, for example, may include multi-tiered structures formed on a nano-scale. These multi-tiered structures can be manufactured using lithography processes, but such processes can be expensive and achieving the desired geometry can be difficult on the nano-scale. For example, fabricating nano-structures that are less than 50 nm with high fidelity (no line breaks, smooth line edges) may use expensive lithography techniques, such as E-beam lithography, to achieve the desired nano-structure resolution. Even with such lithography techniques, aligning components to produce lithography masters and/or a final product at the nanometer scale can be difficult and the resulting nano-structure can be prone to uneven line edge roughness (LER). Thus, there exists a need for an inexpensive process for manufacturing multi-tiered nano-scale structures.

[0008] In order to address the issues associated with expensive lithography techniques used to fabricate nano-structures, systems and methods according to embodiments of this disclosure rely on an ultrasonication process to etch and form the desired nano-structures on a substrate. For example, embodiments according to this disclosure may use an ultrasonication sequence process to achieve desired etch selectivity of the different material layers deposited on a substrate. The ultrasonication

sequence process can include submerging a substrate in a bath of a base solution, acid solution, and/or water and applying ultrasonication to the bath. Systems and methods according to embodiments of this disclosure can etch, for example, silicon-based structures, e.g., Si, SiO₂, Si₃N₄, etc., with multi-tiered nano-structures with high fidelity, smooth LER, and consistent alignment across batches.

BRIEF SUMMARY

[0009] Disclosed herein are systems and methods for fabricating nano-structures on a substrate. The substrate including a plurality of nano-structures can be used in eyepieces for displays, such as for a head wearable device. An example method for fabricating and/or etching a substrate including a plurality of nano-structures for an eyepiece can include submerging the substrate in a bath and applying ultrasonication to the bath for a first time period. The ultrasonication applied to the first bath can agitate the fluid to provide a substantially uniform first reactive environment across the surface of the substrate. The substrate can be submerged in a second bath and ultrasonication can be applied to the second bath for a second time period. The ultrasonication applied to the second bath can agitate the fluid to provide a substantially uniform second reactive environment across the surface of the substrate. In some examples, a predetermined amount of material can be removed from the surface of the substrate during the second time period to produce an etched substrate. In some examples, the predetermined amount of material removed can be based on a length of the first time period and further on a length of the second time period. Embodiments herein provide for a system and method to inexpensively fabricate nano-structures that are less than 50 nm with high fidelity (no line breaks, smooth line edges) to achieve the desired nano-structure resolution. Moreover, embodiments, herein provide for a system and method to achieve alignment between multi-tiered layers of nano-structures with smooth line edge roughness (LER).

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIGS. 1A-1C illustrate an example mixed reality environment, according to one or more embodiments of the disclosure.

[0011] FIGS. 2A-2D illustrate components of an example mixed reality system that can be used to generate and interact with a mixed reality environment, according to one or more embodiments of the disclosure.

[0012] FIG. 3A illustrates an example mixed reality handheld controller that can be used to provide input to a mixed reality environment, according to one or more embodiments of the disclosure.

[0013] FIG. 3B illustrates an example auxiliary unit that can be used with an example mixed reality system, according to one or more embodiments of the disclosure.

[0014] FIG. 4 illustrates an example functional block diagram for an example mixed reality system, according to one or more embodiments of the disclosure.

[0015] FIG. 5 illustrates an example ultrasonication set-up according to one or more embodiments of the disclosure.

[0016] FIGS. 6A-6B illustrate example nano-structures for an example mixed reality system, manufactured according to one or more embodiments of the disclosure.

[0017] FIG. 7A-7C illustrates an example nano-structure for an example mixed reality system, manufactured according to one or more embodiments of the disclosure.

[0018] FIGS. 8A-8B illustrate example nano-structures for an example mixed reality system, manufactured according to one or more embodiments of the disclosure.

[0019] FIGS. 9A-9B illustrate example nano-structures for an example mixed reality system, manufactured according to one or more embodiments of the disclosure.

[0020] FIGS. 10A-10B illustrate example nano-structures for an example mixed reality system,

manufactured according to one or more embodiments of the disclosure.

[0021] FIGS. **11A-11C** illustrates example nano-structures for an example mixed reality system, according to one or more embodiments of the disclosure.

[0022] FIGS. **12A-12C** illustrates example nano-structures for an example mixed reality system, according to one or more embodiments of the disclosure.

[0023] FIGS. **13A-13E** illustrates example nano-structures for an example mixed reality system, according to one or more embodiments of the disclosure.

[0024] FIG. **14** illustrates an example block diagram of a process for manufacturing nano-structures for an example mixed reality system, according to one or more embodiments of the disclosure.

[0025] FIG. **15** illustrates an example block diagram of a process for manufacturing nano-structures for an example mixed reality system, according to one or more embodiments of the disclosure.

[0026] FIG. **16** illustrates an example block diagram of a process for manufacturing nano-structures for an example mixed reality system, according to one or more embodiments of the disclosure.

DETAILED DESCRIPTION

[0027] In the following description of examples, reference is made to the accompanying drawings which form a part hereof, and in which it is shown by way of illustration specific examples that can be practiced. It is to be understood that other examples can be used and structural changes can be made without departing from the scope of the disclosed examples.

Mixed Reality Environment

[0028] Like all people, a user of a mixed reality system exists in a real environment—that is, a three-dimensional portion of the “real world,” and all of its contents, that are perceptible by the user. For example, a user perceives a real environment using one's ordinary human senses—sight, sound, touch, taste, smell—and interacts with the real environment by moving one's own body in the real environment. Locations in a real environment can be described as coordinates in a coordinate space; for example, a coordinate can comprise latitude, longitude, and elevation with respect to sea level; distances in three orthogonal dimensions from a reference point; or other suitable values. Likewise, a vector can describe a quantity having a direction and a magnitude in the coordinate space.

[0029] A computing device can maintain, for example in a memory associated with the device, a representation of a virtual environment. As used herein, a virtual environment is a computational representation of a three-dimensional space. A virtual environment can include representations of any object, action, signal, parameter, coordinate, vector, or other characteristic associated with that space. In some examples, circuitry (e.g., a processor) of a computing device can maintain and update a state of a virtual environment; that is, a processor can determine at a first time t_0 , based on data associated with the virtual environment and/or input provided by a user, a state of the virtual environment at a second time t_1 . For instance, if an object in the virtual environment is located at a first coordinate at time t_0 , and has certain programmed physical parameters (e.g., mass, coefficient of friction); and an input received from user indicates that a force should be applied to the object in a direction vector; the processor can apply laws of kinematics to determine a location of the object at time t_1 using basic mechanics. The processor can use any suitable information known about the virtual environment, and/or any suitable input, to determine a state of the virtual environment at a time t_1 . In maintaining and updating a state of a virtual environment, the processor can execute any suitable software, including software relating to the creation and deletion of virtual objects in the virtual environment; software (e.g., scripts) for defining behavior of virtual objects or characters in the virtual environment; software for defining the behavior of signals (e.g., audio signals) in the virtual environment; software for creating and updating parameters associated with the virtual environment; software for generating audio signals in the virtual environment; software for handling input and output; software for implementing network operations; software for applying asset data (e.g., animation data to move a virtual object over time); or many other possibilities.

[0030] Output devices, such as a display or a speaker, can present any or all aspects of a virtual

environment to a user. For example, a virtual environment may include virtual objects (which may include representations of inanimate objects; people; animals; lights; etc.) that may be presented to a user. A processor can determine a view of the virtual environment (for example, corresponding to a “camera” with an origin coordinate, a view axis, and a frustum); and render, to a display, a viewable scene of the virtual environment corresponding to that view. Any suitable rendering technology may be used for this purpose. In some examples, the viewable scene may include only some virtual objects in the virtual environment, and exclude certain other virtual objects. Similarly, a virtual environment may include audio aspects that may be presented to a user as one or more audio signals. For instance, a virtual object in the virtual environment may generate a sound originating from a location coordinate of the object (e.g., a virtual character may speak or cause a sound effect); or the virtual environment may be associated with musical cues or ambient sounds that may or may not be associated with a particular location. A processor can determine an audio signal corresponding to a “listener” coordinate—for instance, an audio signal corresponding to a composite of sounds in the virtual environment, and mixed and processed to simulate an audio signal that would be heard by a listener at the listener coordinate—and present the audio signal to a user via one or more speakers.

[0031] Because a virtual environment exists only as a computational structure, a user cannot directly perceive a virtual environment using one's ordinary senses. Instead, a user can perceive a virtual environment only indirectly, as presented to the user, for example by a display, speakers, haptic output devices, etc. Similarly, a user cannot directly touch, manipulate, or otherwise interact with a virtual environment; but can provide input data, via input devices or sensors, to a processor that can use the device or sensor data to update the virtual environment. For example, a camera sensor can provide optical data indicating that a user is trying to move an object in a virtual environment, and a processor can use that data to cause the object to respond accordingly in the virtual environment.

[0032] A mixed reality system can present to the user, for example using a transmissible display and/or one or more speakers (which may, for example, be incorporated into a wearable head device), a mixed reality environment (“MRE”) that combines aspects of a real environment and a virtual environment. In some embodiments, the one or more speakers may be external to the head-mounted wearable unit. As used herein, a MRE is a simultaneous representation of a real environment and a corresponding virtual environment. In some examples, the corresponding real and virtual environments share a single coordinate space; in some examples, a real coordinate space and a corresponding virtual coordinate space are related to each other by a transformation matrix (or other suitable representation). Accordingly, a single coordinate (along with, in some examples, a transformation matrix) can define a first location in the real environment, and also a second, corresponding, location in the virtual environment; and vice versa.

[0033] In a MRE, a virtual object (e.g., in a virtual environment associated with the MRE) can correspond to a real object (e.g., in a real environment associated with the MRE). For instance, if the real environment of a MRE comprises a real lamp post (a real object) at a location coordinate, the virtual environment of the MRE may comprise a virtual lamp post (a virtual object) at a corresponding location coordinate. As used herein, the real object in combination with its corresponding virtual object together constitute a “mixed reality object.” It is not necessary for a virtual object to perfectly match or align with a corresponding real object. In some examples, a virtual object can be a simplified version of a corresponding real object. For instance, if a real environment includes a real lamp post, a corresponding virtual object may comprise a cylinder of roughly the same height and radius as the real lamp post (reflecting that lamp posts may be roughly cylindrical in shape). Simplifying virtual objects in this manner can allow computational efficiencies, and can simplify calculations to be performed on such virtual objects. Further, in some examples of a MRE, not all real objects in a real environment may be associated with a corresponding virtual object. Likewise, in some examples of a MRE, not all virtual objects in a

virtual environment may be associated with a corresponding real object. That is, some virtual objects may solely in a virtual environment of a MRE, without any real-world counterpart. [0034] In some examples, virtual objects may have characteristics that differ, sometimes drastically, from those of corresponding real objects. For instance, while a real environment in a MRE may comprise a green, two-armed cactus—a prickly inanimate object—a corresponding virtual object in the MRE may have the characteristics of a green, two-armed virtual character with human facial features and a surly demeanor. In this example, the virtual object resembles its corresponding real object in certain characteristics (color, number of arms); but differs from the real object in other characteristics (facial features, personality). In this way, virtual objects have the potential to represent real objects in a creative, abstract, exaggerated, or fanciful manner; or to impart behaviors (e.g., human personalities) to otherwise inanimate real objects. In some examples, virtual objects may be purely fanciful creations with no real-world counterpart (e.g., a virtual monster in a virtual environment, perhaps at a location corresponding to an empty space in a real environment).

[0035] Compared to VR systems, which present the user with a virtual environment while obscuring the real environment, a mixed reality system presenting a MRE affords the advantage that the real environment remains perceptible while the virtual environment is presented. Accordingly, the user of the mixed reality system is able to use visual and audio cues associated with the real environment to experience and interact with the corresponding virtual environment. As an example, while a user of VR systems may struggle to perceive or interact with a virtual object displayed in a virtual environment—because, as noted above, a user cannot directly perceive or interact with a virtual environment—a user of an MR system may find it intuitive and natural to interact with a virtual object by seeing, hearing, and touching a corresponding real object in his or her own real environment. This level of interactivity can heighten a user's feelings of immersion, connection, and engagement with a virtual environment. Similarly, by simultaneously presenting a real environment and a virtual environment, mixed reality systems can reduce negative psychological feelings (e.g., cognitive dissonance) and negative physical feelings (e.g., motion sickness) associated with VR systems. Mixed reality systems further offer many possibilities for applications that may augment or alter our experiences of the real world.

[0036] FIG. 1A illustrates an example real environment **100** in which a user **110** uses a mixed reality system **112**. Mixed reality system **112** may comprise a display (e.g., a transmissible display) and one or more speakers, and one or more sensors (e.g., a camera), for example as described below. The real environment **100** shown comprises a rectangular room **104A**, in which user **110** is standing; and real objects **122A** (a lamp), **124A** (a table), **126A** (a sofa), and **128A** (a painting). Room **104A** further comprises a location coordinate **106**, which may be considered an origin of the real environment **100**. As shown in FIG. 1A, an environment/world coordinate system **108** (comprising an x-axis **108X**, a y-axis **108Y**, and a z-axis **108Z**) with its origin at point **106** (a world coordinate), can define a coordinate space for real environment **100**. In some embodiments, the origin point **106** of the environment/world coordinate system **108** may correspond to where the mixed reality system **112** was powered on. In some embodiments, the origin point **106** of the environment/world coordinate system **108** may be reset during operation. In some examples, user **110** may be considered a real object in real environment **100**; similarly, user **110**'s body parts (e.g., hands, feet) may be considered real objects in real environment **100**. In some examples, a user/listener/head coordinate system **114** (comprising an x-axis **114X**, a y-axis **114Y**, and a z-axis **114Z**) with its origin at point **115** (e.g., user/listener/head coordinate) can define a coordinate space for the user/listener/head on which the mixed reality system **112** is located. The origin point **115** of the user/listener/head coordinate system **114** may be defined relative to one or more components of the mixed reality system **112**. For example, the origin point **115** of the user/listener/head coordinate system **114** may be defined relative to the display of the mixed reality system **112** such as during initial calibration of the mixed reality system **112**. A matrix (which may include a translation matrix and a Quaternion matrix or other rotation matrix), or other suitable representation can characterize

a transformation between the user/listener/head coordinate system **114** space and the environment/world coordinate system **108** space. In some embodiments, a left ear coordinate **116** and a right ear coordinate **117** may be defined relative to the origin point **115** of the user/listener/head coordinate system **114**. A matrix (which may include a translation matrix and a Quaternion matrix or other rotation matrix), or other suitable representation can characterize a transformation between the left ear coordinate **116** and the right ear coordinate **117**, and user/listener/head coordinate system **114** space. The user/listener/head coordinate system **114** can simplify the representation of locations relative to the user's head, or to a head-mounted device, for example, relative to the environment/world coordinate system **108**. Using Simultaneous Localization and Mapping (SLAM), visual odometry, or other techniques, a transformation between user coordinate system **114** and environment coordinate system **108** can be determined and updated in real-time.

[0037] FIG. **1B** illustrates an example virtual environment **130** that corresponds to real environment **100**. The virtual environment **130** shown comprises a virtual rectangular room **104B** corresponding to real rectangular room **104A**; a virtual object **122B** corresponding to real object **122A**; a virtual object **124B** corresponding to real object **124A**; and a virtual object **126B** corresponding to real object **126A**. Metadata associated with the virtual objects **122B**, **124B**, **126B** can include information derived from the corresponding real objects **122A**, **124A**, and **126A**. Virtual environment **130** additionally comprises a virtual monster **132**, which does not correspond to any real object in real environment **100**. Real object **128A** in real environment **100** does not correspond to any virtual object in virtual environment **130**. A persistent coordinate system **133** (comprising an x-axis **133X**, a y-axis **133Y**, and a z-axis **133Z**) with its origin at point **134** (persistent coordinate), can define a coordinate space for virtual content. The origin point **134** of the persistent coordinate system **133** may be defined relative/with respect to one or more real objects, such as the real object **126A**. A matrix (which may include a translation matrix and a Quaternion matrix or other rotation matrix), or other suitable representation can characterize a transformation between the persistent coordinate system **133** space and the environment/world coordinate system **108** space. In some embodiments, each of the virtual objects **122B**, **124B**, **126B**, and **132** may have their own persistent coordinate point relative to the origin point **134** of the persistent coordinate system **133**. In some embodiments, there may be multiple persistent coordinate systems and each of the virtual objects **122B**, **124B**, **126B**, and **132** may have their own persistent coordinate point relative to one or more persistent coordinate systems.

[0038] Persistent coordinate data may be coordinate data that persists relative to a physical environment. Persistent coordinate data may be used by MR systems (e.g., MR system **112**, **200**) to place persistent virtual content, which may not be tied to movement of a display on which the virtual object is being displayed. For example, a two-dimensional screen may only display virtual objects relative to a position on the screen. As the two-dimensional screen moves, the virtual content may move with the screen. In some embodiments, persistent virtual content may be displayed in a corner of a room. A MR user may look at the corner, see the virtual content, look away from the corner (where the virtual content may no longer be visible because the virtual content may have moved from within the user's field of view to a location outside the user's field of view due to motion of the user's head), and look back to see the virtual content in the corner (similar to how a real object may behave).

[0039] In some embodiments, persistent coordinate data (e.g., a persistent coordinate system and/or a persistent coordinate frame) can include an origin point and three axes. For example, a persistent coordinate system may be assigned to a center of a room by a MR system. In some embodiments, a user may move around the room, out of the room, re-enter the room, etc., and the persistent coordinate system may remain at the center of the room (e.g., because it persists relative to the physical environment). In some embodiments, a virtual object may be displayed using a transform to persistent coordinate data, which may enable displaying persistent virtual content. In some

embodiments, a MR system may use simultaneous localization and mapping to generate persistent coordinate data (e.g., the MR system may assign a persistent coordinate system to a point in space). In some embodiments, a MR system may map an environment by generating persistent coordinate data at regular intervals (e.g., a MR system may assign persistent coordinate systems in a grid where persistent coordinate systems may be at least within five feet of another persistent coordinate system).

[0040] In some embodiments, persistent coordinate data may be generated by a MR system and transmitted to a remote server. In some embodiments, a remote server may be configured to receive persistent coordinate data. In some embodiments, a remote server may be configured to synchronize persistent coordinate data from multiple observation instances. For example, multiple MR systems may map the same room with persistent coordinate data and transmit that data to a remote server. In some embodiments, the remote server may use this observation data to generate canonical persistent coordinate data, which may be based on the one or more observations. In some embodiments, canonical persistent coordinate data may be more accurate and/or reliable than a single observation of persistent coordinate data. In some embodiments, canonical persistent coordinate data may be transmitted to one or more MR systems. For example, a MR system may use image recognition and/or location data to recognize that it is located in a room that has corresponding canonical persistent coordinate data (e.g., because other MR systems have previously mapped the room). In some embodiments, the MR system may receive canonical persistent coordinate data corresponding to its location from a remote server.

[0041] With respect to FIGS. 1A and 1B, environment/world coordinate system **108** defines a shared coordinate space for both real environment **100** and virtual environment **130**. In the example shown, the coordinate space has its origin at point **106**. Further, the coordinate space is defined by the same three orthogonal axes (**108X**, **108Y**, **108Z**). Accordingly, a first location in real environment **100**, and a second, corresponding location in virtual environment **130**, can be described with respect to the same coordinate space. This simplifies identifying and displaying corresponding locations in real and virtual environments, because the same coordinates can be used to identify both locations. However, in some examples, corresponding real and virtual environments need not use a shared coordinate space. For instance, in some examples (not shown), a matrix (which may include a translation matrix and a Quaternion matrix or other rotation matrix), or other suitable representation can characterize a transformation between a real environment coordinate space and a virtual environment coordinate space.

[0042] FIG. 1C illustrates an example MRE **150** that simultaneously presents aspects of real environment **100** and virtual environment **130** to user **110** via mixed reality system **112**. In the example shown, MRE **150** simultaneously presents user **110** with real objects **122A**, **124A**, **126A**, and **128A** from real environment **100** (e.g., via a transmissible portion of a display of mixed reality system **112**); and virtual objects **122B**, **124B**, **126B**, and **132** from virtual environment **130** (e.g., via an active display portion of the display of mixed reality system **112**). As above, origin point **106** acts as an origin for a coordinate space corresponding to MRE **150**, and coordinate system **108** defines an x-axis, y-axis, and z-axis for the coordinate space.

[0043] In the example shown, mixed reality objects comprise corresponding pairs of real objects and virtual objects (i.e., **122A/122B**, **124A/124B**, **126A/126B**) that occupy corresponding locations in coordinate space **108**. In some examples, both the real objects and the virtual objects may be simultaneously visible to user **110**. This may be desirable in, for example, instances where the virtual object presents information designed to augment a view of the corresponding real object (such as in a museum application where a virtual object presents the missing pieces of an ancient damaged sculpture). In some examples, the virtual objects (**122B**, **124B**, and/or **126B**) may be displayed (e.g., via active pixelated occlusion using a pixelated occlusion shutter) so as to occlude the corresponding real objects (**122A**, **124A**, and/or **126A**). This may be desirable in, for example, instances where the virtual object acts as a visual replacement for the corresponding real object

(such as in an interactive storytelling application where an inanimate real object becomes a “living” character).

[0044] In some examples, real objects (e.g., **122A**, **124A**, **126A**) may be associated with virtual content or helper data that may not necessarily constitute virtual objects. Virtual content or helper data can facilitate processing or handling of virtual objects in the mixed reality environment. For example, such virtual content could include two-dimensional representations of corresponding real objects; custom asset types associated with corresponding real objects; or statistical data associated with corresponding real objects. This information can enable or facilitate calculations involving a real object without incurring unnecessary computational overhead.

[0045] In some examples, the presentation described above may also incorporate audio aspects. For instance, in MRE **150**, virtual monster **132** could be associated with one or more audio signals, such as a footstep sound effect that is generated as the monster walks around MRE **150**. As described further below, a processor of mixed reality system **112** can compute an audio signal corresponding to a mixed and processed composite of all such sounds in MRE **150**, and present the audio signal to user **110** via one or more speakers included in mixed reality system **112** and/or one or more external speakers.

Example Mixed Reality System

[0046] Example mixed reality system **112** can include a wearable head device (e.g., a wearable augmented reality or mixed reality head device) comprising a display (which may comprise left and right transmissible displays, which may be near-eye displays, and associated components for coupling light from the displays to the user's eyes); left and right speakers (e.g., positioned adjacent to the user's left and right ears, respectively); an inertial measurement unit (IMU) (e.g., mounted to a temple arm of the head device); an orthogonal coil electromagnetic receiver (e.g., mounted to the left temple piece); left and right cameras (e.g., depth (time-of-flight) cameras) oriented away from the user; and left and right eye cameras oriented toward the user (e.g., for detecting the user's eye movements). However, a mixed reality system **112** can incorporate any suitable display technology, and any suitable sensors (e.g., optical, infrared, acoustic, LIDAR, EOG, GPS, magnetic). In addition, mixed reality system **112** may incorporate networking features (e.g., Wi-Fi capability) to communicate with other devices and systems, including other mixed reality systems. Mixed reality system **112** may further include a battery (which may be mounted in an auxiliary unit, such as a belt pack designed to be worn around a user's waist), a processor, and a memory. The wearable head device of mixed reality system **112** may include tracking components, such as an IMU or other suitable sensors, configured to output a set of coordinates of the wearable head device relative to the user's environment. In some examples, tracking components may provide input to a processor performing a Simultaneous Localization and Mapping (SLAM) and/or visual odometry algorithm. In some examples, mixed reality system **112** may also include a handheld controller **300**, and/or an auxiliary unit **320**, which may be a wearable backpack, as described further below.

[0047] FIGS. 2A-2D illustrate components of an example mixed reality system **200** (which may correspond to mixed reality system **112**) that may be used to present a MRE (which may correspond to MRE **150**), or other virtual environment, to a user. FIG. 2A illustrates a perspective view of a wearable head device **2102** included in example mixed reality system **200**. FIG. 2B illustrates a top view of wearable head device **2102** worn on a user's head **2202**. FIG. 2C illustrates a front view of wearable head device **2102**. FIG. 2D illustrates an edge view of example eyepiece **2110** of wearable head device **2102**. As shown in FIGS. 2A-2C, the example wearable head device **2102** includes an example left eyepiece (e.g., a left transparent waveguide set eyepiece) **2108** and an example right eyepiece (e.g., a right transparent waveguide set eyepiece) **2110**. Each eyepiece **2108** and **2110** can include transmissible elements through which a real environment can be visible, as well as display elements for presenting a display (e.g., via imagewise modulated light) overlapping the real environment. In some examples, such display elements can include surface diffractive optical elements for controlling the flow of imagewise modulated light. For instance, the

left eyepiece **2108** can include a left in-coupling grating set **2112**, a left orthogonal pupil expansion (OPE) grating set **2120**, and a left exit (output) pupil expansion (EPE) grating set **2122**. As used herein, a pupil may refer to the exit of light from an optical element such as a grating set or reflector. Similarly, the right eyepiece **2110** can include a right in-coupling grating set **2118**, a right OPE grating set **2114** and a right EPE grating set **2116**. Imagewise modulated light can be transferred to a user's eye via the in-coupling gratings **2112** and **2118**, OPEs **2114** and **2120**, and EPE **2116** and **2122**. Each in-coupling grating set **2112**, **2118** can be configured to deflect light toward its corresponding OPE grating set **2120**, **2114**. Each OPE grating set **2120**, **2114** can be designed to incrementally deflect light down toward its associated EPE **2122**, **2116**, thereby horizontally extending an exit pupil being formed. Each EPE **2122**, **2116** can be configured to incrementally redirect at least a portion of light received from its corresponding OPE grating set **2120**, **2114** outward to a user eyepiece position (not shown) defined behind the eyepieces **2108**, **2110**, vertically extending the exit pupil that is formed at the eyepiece. Alternatively, in lieu of the in-coupling grating sets **2112** and **2118**, OPE grating sets **2114** and **2120**, and EPE grating sets **2116** and **2122**, the eyepieces **2108** and **2110** can include other arrangements of gratings and/or refractive and reflective features for controlling the coupling of imagewise modulated light to the user's eyes. [0048] In some examples, wearable head device **2102** can include a left temple arm **2130** and a right temple arm **2132**, where the left temple arm **2130** includes a left speaker **2134** and the right temple arm **2132** includes a right speaker **2136**. An orthogonal coil electromagnetic receiver **2138** can be located in the left temple piece, or in another suitable location in the wearable head unit **2102**. An Inertial Measurement Unit (IMU) **2140** can be located in the right temple arm **2132**, or in another suitable location in the wearable head device **2102**. The wearable head device **2102** can also include a left depth (e.g., time-of-flight) camera **2142** and a right depth camera **2144**. The depth cameras **2142**, **2144** can be suitably oriented in different directions so as to together cover a wider field of view.

[0049] In the example shown in FIGS. 2A-2D, a left source of imagewise modulated light **2124** can be optically coupled into the left eyepiece **2108** through the left in-coupling grating set **2112**, and a right source of imagewise modulated light **2126** can be optically coupled into the right eyepiece **2110** through the right in-coupling grating set **2118**. Sources of imagewise modulated light **2124**, **2126** can include, for example, optical fiber scanners; projectors including electronic light modulators such as Digital Light Processing (DLP) chips or Liquid Crystal on Silicon (LCoS) modulators; or emissive displays, such as micro Light Emitting Diode (μ LED) or micro Organic Light Emitting Diode (μ OLED) panels coupled into the in-coupling grating sets **2112**, **2118** using one or more lenses per side. The input coupling grating sets **2112**, **2118** can deflect light from the sources of imagewise modulated light **2124**, **2126** to angles above the critical angle for Total Internal Reflection (TIR) for the eyepieces **2108**, **2110**. The OPE grating sets **2114**, **2120** incrementally deflect light propagating by TIR down toward the EPE grating sets **2116**, **2122**. The EPE grating sets **2116**, **2122** incrementally couple light toward the user's face, including the pupils of the user's eyes.

[0050] In some examples, as shown in FIG. 2D, each of the left eyepiece **2108** and the right eyepiece **2110** includes a plurality of waveguides **2402**. For example, each eyepiece **2108**, **2110** can include multiple individual waveguides, each dedicated to a respective color channel (e.g., red, blue and green). In some examples, each eyepiece **2108**, **2110** can include multiple sets of such waveguides, with each set configured to impart different wavefront curvature to emitted light. The wavefront curvature may be convex with respect to the user's eyes, for example to present a virtual object positioned a distance in front of the user (e.g., by a distance corresponding to the reciprocal of wavefront curvature). In some examples, EPE grating sets **2116**, **2122** can include curved grating grooves to effect convex wavefront curvature by altering the Poynting vector of exiting light across each EPE.

[0051] In some examples, to create a perception that displayed content is three-dimensional,

stereoscopically-adjusted left and right eye imagery can be presented to the user through the imagewise light modulators **2124**, **2126** and the eyepieces **2108**, **2110**. The perceived realism of a presentation of a three-dimensional virtual object can be enhanced by selecting waveguides (and thus corresponding the wavefront curvatures) such that the virtual object is displayed at a distance approximating a distance indicated by the stereoscopic left and right images. This technique may also reduce motion sickness experienced by some users, which may be caused by differences between the depth perception cues provided by stereoscopic left and right eye imagery, and the autonomic accommodation (e.g., object distance-dependent focus) of the human eye.

[0052] FIG. 2D illustrates an edge-facing view from the top of the right eyepiece **2110** of example wearable head device **2102**. As shown in FIG. 2D, the plurality of waveguides **2402** can include a first subset of three waveguides **2404** and a second subset of three waveguides **2406**. The two subsets of waveguides **2404**, **2406** can be differentiated by different EPE gratings featuring different grating line curvatures to impart different wavefront curvatures to exiting light. Within each of the subsets of waveguides **2404**, **2406** each waveguide can be used to couple a different spectral channel (e.g., one of red, green and blue spectral channels) to the user's right eye **2206**. (Although not shown in FIG. 2D, the structure of the left eyepiece **2108** is analogous to the structure of the right eyepiece **2110**.)

[0053] FIG. 3A illustrates an example handheld controller component **300** of a mixed reality system **200**. In some examples, handheld controller **300** includes a grip portion **346** and one or more buttons **350** disposed along a top surface **348**. In some examples, buttons **350** may be configured for use as an optical tracking target, e.g., for tracking six-degree-of-freedom (6DOF) motion of the handheld controller **300**, in conjunction with a camera or other optical sensor (which may be mounted in a head unit (e.g., wearable head device **2102**) of mixed reality system **200**). In some examples, handheld controller **300** includes tracking components (e.g., an IMU or other suitable sensors) for detecting position or orientation, such as position or orientation relative to wearable head device **2102**. In some examples, such tracking components may be positioned in a handle of handheld controller **300**, and/or may be mechanically coupled to the handheld controller. Handheld controller **300** can be configured to provide one or more output signals corresponding to one or more of a pressed state of the buttons; or a position, orientation, and/or motion of the handheld controller **300** (e.g., via an IMU). Such output signals may be used as input to a processor of mixed reality system **200**. Such input may correspond to a position, orientation, and/or movement of the handheld controller (and, by extension, to a position, orientation, and/or movement of a hand of a user holding the controller). Such input may also correspond to a user pressing buttons **350**.

[0054] FIG. 3B illustrates an example auxiliary unit **320** of a mixed reality system **200**. The auxiliary unit **320** can include a battery to provide energy to operate the system **200**, and can include a processor for executing programs to operate the system **200**. As shown, the example auxiliary unit **320** includes a clip **2128**, such as for attaching the auxiliary unit **320** to a user's belt. Other form factors are suitable for auxiliary unit **320** and will be apparent, including form factors that do not involve mounting the unit to a user's belt. In some examples, auxiliary unit **320** is coupled to the wearable head device **2102** through a multiconduit cable that can include, for example, electrical wires and fiber optics. Wireless connections between the auxiliary unit **320** and the wearable head device **2102** can also be used.

[0055] In some examples, mixed reality system **200** can include one or more microphones to detect sound and provide corresponding signals to the mixed reality system. In some examples, a microphone may be attached to, or integrated with, wearable head device **2102**, and may be configured to detect a user's voice. In some examples, a microphone may be attached to, or integrated with, handheld controller **300** and/or auxiliary unit **320**. Such a microphone may be configured to detect environmental sounds, ambient noise, voices of a user or a third party, or other sounds.

[0056] FIG. 4 shows an example functional block diagram that may correspond to an example mixed reality system, such as mixed reality system **200** described above (which may correspond to mixed reality system **112** with respect to FIG. 1). As shown in FIG. 4, example handheld controller **400B** (which may correspond to handheld controller **300** (a “totem”)) includes a totem-to-wearable head device six degree of freedom (6DOF) totem subsystem **404A** and example wearable head device **400A** (which may correspond to wearable head device **2102**) includes a totem-to-wearable head device 6DOF subsystem **404B**. In the example, the 6DOF totem subsystem **404A** and the 6DOF subsystem **404B** cooperate to determine six coordinates (e.g., offsets in three translation directions and rotation along three axes) of the handheld controller **400B** relative to the wearable head device **400A**. The six degrees of freedom may be expressed relative to a coordinate system of the wearable head device **400A**. The three translation offsets may be expressed as X, Y, and Z offsets in such a coordinate system, as a translation matrix, or as some other representation. The rotation degrees of freedom may be expressed as sequence of yaw, pitch and roll rotations, as a rotation matrix, as a quaternion, or as some other representation. In some examples, the wearable head device **400A**; one or more depth cameras **444** (and/or one or more non-depth cameras) included in the wearable head device **400A**; and/or one or more optical targets (e.g., buttons **350** of handheld controller **400B** as described above, or dedicated optical targets included in the handheld controller **400B**) can be used for 6DOF tracking. In some examples, the handheld controller **400B** can include a camera, as described above; and the wearable head device **400A** can include an optical target for optical tracking in conjunction with the camera. In some examples, the wearable head device **400A** and the handheld controller **400B** each include a set of three orthogonally oriented solenoids which are used to wirelessly send and receive three distinguishable signals. By measuring the relative magnitude of the three distinguishable signals received in each of the coils used for receiving, the 6DOF of the wearable head device **400A** relative to the handheld controller **400B** may be determined. Additionally, 6DOF totem subsystem **404A** can include an Inertial Measurement Unit (IMU) that is useful to provide improved accuracy and/or more timely information on rapid movements of the handheld controller **400B**.

[0057] In some embodiments, wearable system **400** can include microphone array **407**, which can include one or more microphones arranged on headgear device **400A**. In some embodiments, microphone array **407** can include four microphones. Two microphones can be placed on a front face of headgear **400A**, and two microphones can be placed at a rear of head headgear **400A** (e.g., one at a back-left and one at a back-right). In some embodiments, signals received by microphone array **407** can be transmitted to DSP **408**. DSP **408** can be configured to perform signal processing on the signals received from microphone array **407**. For example, DSP **408** can be configured to perform noise reduction, acoustic echo cancellation, and/or beamforming on signals received from microphone array **407**. DSP **408** can be configured to transmit signals to processor **416**.

[0058] In some examples, it may become necessary to transform coordinates from a local coordinate space (e.g., a coordinate space fixed relative to the wearable head device **400A**) to an inertial coordinate space (e.g., a coordinate space fixed relative to the real environment), for example in order to compensate for the movement of the wearable head device **400A** relative to the coordinate system **108**. For instance, such transformations may be necessary for a display of the wearable head device **400A** to present a virtual object at an expected position and orientation relative to the real environment (e.g., a virtual person sitting in a real chair, facing forward, regardless of the wearable head device's position and orientation), rather than at a fixed position and orientation on the display (e.g., at the same position in the right lower corner of the display), to preserve the illusion that the virtual object exists in the real environment (and does not, for example, appear positioned unnaturally in the real environment as the wearable head device **400A** shifts and rotates). In some examples, a compensatory transformation between coordinate spaces can be determined by processing imagery from the depth cameras **444** using a SLAM and/or visual odometry procedure in order to determine the transformation of the wearable head device **400A**.

relative to the coordinate system **108**. In the example shown in FIG. **4**, the depth cameras **444** are coupled to a SLAM/visual odometry block **406** and can provide imagery to block **406**. The SLAM/visual odometry block **406** implementation can include a processor configured to process this imagery and determine a position and orientation of the user's head, which can then be used to identify a transformation between a head coordinate space and another coordinate space (e.g., an inertial coordinate space). Similarly, in some examples, an additional source of information on the user's head pose and location is obtained from an IMU **409**. Information from the IMU **409** can be integrated with information from the SLAM/visual odometry block **406** to provide improved accuracy and/or more timely information on rapid adjustments of the user's head pose and position. [0059] In some examples, the depth cameras **444** can supply 3D imagery to a hand gesture tracker **411**, which may be implemented in a processor of the wearable head device **400A**. The hand gesture tracker **411** can identify a user's hand gestures, for example by matching 3D imagery received from the depth cameras **444** to stored patterns representing hand gestures. Other suitable techniques of identifying a user's hand gestures will be apparent.

[0060] In some examples, one or more processors **416** may be configured to receive data from the wearable head device's 6DOF headgear subsystem **404B**, the IMU **409**, the SLAM/visual odometry block **406**, depth cameras **444**, and/or the hand gesture tracker **411**. The processor **416** can also send and receive control signals from the 6DOF totem system **404A**. The processor **416** may be coupled to the 6DOF totem system **404A** wirelessly, such as in examples where the handheld controller **400B** is untethered. Processor **416** may further communicate with additional components, such as an audio-visual content memory **418**, a Graphical Processing Unit (GPU) **420**, and/or a Digital Signal Processor (DSP) audio spatializer **422**. The DSP audio spatializer **422** may be coupled to a Head Related Transfer Function (HRTF) memory **425**. The GPU **420** can include a left channel output coupled to the left source of imagewise modulated light **424** and a right channel output coupled to the right source of imagewise modulated light **426**. GPU **420** can output stereoscopic image data to the sources of imagewise modulated light **424**, **426**, for example as described above with respect to FIGS. **2A-2D**. The DSP audio spatializer **422** can output audio to a left speaker **412** and/or a right speaker **414**. The DSP audio spatializer **422** can receive input from processor **419** indicating a direction vector from a user to a virtual sound source (which may be moved by the user, e.g., via the handheld controller **320**). Based on the direction vector, the DSP audio spatializer **422** can determine a corresponding HRTF (e.g., by accessing a HRTF, or by interpolating multiple HRTFs). The DSP audio spatializer **422** can then apply the determined HRTF to an audio signal, such as an audio signal corresponding to a virtual sound generated by a virtual object. This can enhance the believability and realism of the virtual sound, by incorporating the relative position and orientation of the user relative to the virtual sound in the mixed reality environment—that is, by presenting a virtual sound that matches a user's expectations of what that virtual sound would sound like if it were a real sound in a real environment.

[0061] In some examples, such as shown in FIG. **4**, one or more of processor **416**, GPU **420**, DSP audio spatializer **422**, HRTF memory **425**, and audio/visual content memory **418** may be included in an auxiliary unit **400C** (which may correspond to auxiliary unit **320** described above). The auxiliary unit **400C** may include a battery **427** to power its components and/or to supply power to the wearable head device **400A** or handheld controller **400B**. Including such components in an auxiliary unit, which can be mounted to a user's waist, can limit the size and weight of the wearable head device **400A**, which can in turn reduce fatigue of a user's head and neck.

[0062] While FIG. **4** presents elements corresponding to various components of an example mixed reality system, various other suitable arrangements of these components will become apparent to those skilled in the art. For example, elements presented in FIG. **4** as being associated with auxiliary unit **400C** could instead be associated with the wearable head device **400A** or handheld controller **400B**. Furthermore, some mixed reality systems may forgo entirely a handheld controller **400B** or auxiliary unit **400C**. Such changes and modifications are to be understood as being

included within the scope of the disclosed examples.

Ultrasonication for Nano-Structure Fabrication

[0063] A wearable head device or head mounted display of an example mixed reality system (e.g., mixed reality system **200**) may include an optical system with an eyepiece for presenting an image to a user via the display. The eyepiece can include one or more optical gratings (e.g., in-coupling grating set **2112**, left orthogonal pupil expansion (OPE) grating set **2120**, and left exit (output) pupil expansion (EPE) grating set **2122**, right eyepiece **2110** can include a right in-coupling grating set **2118**, a right OPE grating set **2114** and a right EPE grating set **2116**). The one or more optical gratings can be used to transfer imagewise light to a user's eye.

[0064] As discussed above, nano-structures that form the optical gratings can be fabricated with lithography processes. The nano-structures can be multi-tier symmetric and/or asymmetric. However, fabricating nano-structures using lithography can be expensive and complex. For example, fabricating nano-structures that are less than 50 nm with high fidelity (no line breaks, smooth line edges) may use expensive lithography techniques, such as E-beam lithography, to achieve the desired nano-structure resolution. Even with such lithography techniques, aligning components to produce lithography masters and/or a final product at the nanometer scale can be difficult and the resulting nano-structure can be prone to uneven line edge roughness (LER).

[0065] In order to address the issues associated with expensive lithography techniques used to fabricate nano-structures, systems and methods according to embodiments of this disclosure rely on an ultrasonication process to etch and form the desired nano-structures on a substrate. For example, embodiments according to this disclosure may use an ultrasonication sequence process to achieve desired etch selectivity of the different material layers deposited on a substrate. The ultrasonication sequence process can include submerging a substrate in a bath of a base solution, acid solution, and/or water and applying ultrasonication to the bath. Systems and methods according to embodiments of this disclosure can etch, for example, silicon-based structures, e.g., Si, SiO₂, Si₃N₄, etc., with multi-tiered nano-structures with high fidelity, smooth LER, and consistent alignment across batches.

[0066] As used herein, ultrasonication may refer to a process of applying sound energy and agitation using a transducer to a vessel containing a fluid as a medium to provide reactive etch species and/or remove away reacted species, residue, particles, debris, etc. FIG. 5 illustrates an example of an exemplary ultrasonication set-up **500** according to embodiments of this disclosure. The exemplary set-up **500** can include at least a transducer **502**, a vessel **504**, and a liquid bath **506**. The transducer **502** may be provided to apply sound waves to the vessel **504**. For example, the transducer can provide waves at 20-200 KHz. The liquid bath, e.g., a fluid, can be a base solution, an acid solution and/or water. In some embodiments, the acid solutions can include sulfuric acid, citric acid, etc. In some embodiments, the base solutions can include potassium hydroxide and/or hydrogen peroxide. In some examples, the acid and base solutions can have chemical concentration of about 1-20% with a pH ranging from about 3-11. In some embodiments, the energy from the transducer can be pulsed at certain intervals rather than being continuously pulsed.

[0067] As shown in the figure, the substrate **508** to be etched may be placed in the vessel **504**. In one or more examples, the substrate can be formed from silicon, silicon dioxide, silicon nitride, and/or other silicon-based substrate materials. In some embodiments, the liquid bath of the ultrasonication set-up **500** may be at a room temperature during the ultrasonication process. In some embodiments, the liquid bath of the ultrasonication set-up may be at an elevated temperature, e.g., above room temperature about 40-80 C. For example, a heater (not shown) can be coupled to the vessel **504** to achieve a desired temperature for the liquid bath **506**.

[0068] In one or more examples, the substrate **508** can be sequentially placed in a bath of a base solution, an acid solution, and/or water. As the substrate **508** is submerged in the liquid bath **506**, the transducer **502** can apply sound waves to the vessel **504**. The waves can agitate the fluid in the vessel **504**. In this manner, ultrasonication can assist the reaction between the fluid and the

substrate as well as the removal rate of the reacted species, e.g., etched material, and reacted solution away from the substrate surface and replenish the substrate surface with a new reactive environment, e.g., unreacted solution, for the reaction to continue. In some examples, acid and/or base solutions may be selected based on its reactivity with the substrate material. For example, the acid and/or base solutions may be selected based on their ability to react with a surface of the substrate material and remove, e.g., etch away, material from a surface of the substrate **508**.

[0069] In some examples, a plurality of hydrolysis reactions occurring at the surface of the substrate **508** can gradually remove the silicon material. For example, hydrolysis of the silicon dioxide bond can occur on the substrate **508** surface due to proton transfer from hydronium ions (H_3O^+), hydroxide (OH^-), and/or hydrogen-bonded complex molecules present in the acid and/or base solutions. For instance, at the solid to liquid (e.g., silicon dioxide to solution) interface silanol ($\text{Si}-\text{OH}$) bonds can be created thereby reducing the energy barrier of silicon dioxide and silanol bonds. This can result in an increase in reaction by protonation due to the smaller energy requirement to break the bonds between molecules. The energy barrier reduction can also result from the presence of h-bonded complexes in the water solution, which can contribute to proton transfer. The equations that govern the acid and base protonation reaction for silicon with silanol present at the substrate surface to solution interface, is provided given below equations 1 and 2.



[0070] Table 1 shows exemplary etch rates of silicon and silicon dioxide nano-structures using ultrasonication processes according to embodiments of this disclosure. As used herein, the etch rate can be used to refer to the rate of material removal from a surface of a substrate. In some embodiments, submerging the substrate in the liquid bath and applying ultrasonication to the bath can provide a substantially uniform reactive environment across the surface of the substrate, thereby providing substantially uniform etching and material removal across the substrate surface. The example shown in table 1 can correspond to treating a substrate in with a base solution (2% base solution with a pH of 11 in water) for about 8 minutes at about 60 C and an acid solution (2% acid solution with a pH of 3 in water) for about 20 minutes at about 60 C). The concentrations of the base and acid solutions are exemplary and not intended to limit the scope of this disclosure. Moreover, the etch rates shown in Table 1 are exemplary and can vary with different ultrasonication conditions, e.g., temperature, acid and/or base solution concentration, and length of time of the ultrasonication process. In some embodiments, the ultrasonication conditions can be tuned to provide a steady and/or consistent etch rate.

TABLE-US-00001

Process Sequence	Si	SiO ₂
Base, Water	0 nm/min	0 nm/min
Acid, Water	0 nm/min	0 nm/min
Base, Acid, Water	1 nm/min~4 nm/min	0.2~0.7 nm/min
Base, Water, Acid, Water	1 nm/min~4 nm/min	<0 nm/min

[0071] As shown in the table, treating a silicon substrate and/or a silicon dioxide substrate with a base-water process sequence (e.g., submerging the substrate in base solution bath and applying ultrasonication, followed by submerging the substrate in a water bath and applying ultrasonication) may not result in a discernable removal of material from the surface of the substrate. Similarly, treating a silicon substrate and a silicon dioxide substrate with an acid-water process sequence (e.g., submerging the substrate in base solution acid and applying ultrasonication, followed by submerging the substrate in a water bath and applying ultrasonication) may not result in a discernable removal of material from the surface of the substrate.

[0072] However, base-acid-water and base-water-acid-water process sequences may result in discernable etch rates. As seen in Table 1, silicon and silicon dioxide are each associated with different etch rates for different process sequences. This difference in etch rate may be attributed to a weaker energy barrier associated with silicon bonds compared to silicon oxide bonds. For

example, the O—Si—O bonds may be stronger in silicon dioxide and lead to a slower hydrolysis reaction, see e.g., Equations 1 and 2, and material removal. For example, treating a silicon substrate with a base-acid-water process sequence can provide an etch rate of about 1-4 nm/min, while treating a silicon dioxide substrate with the same base-acid-water process (e.g., the same solution strength, time, and temperature) resulted in an etch rate of about 0.2-0.7 nm/min. Similarly, treating a silicon substrate with a base-water-acid-water process sequence provided an etch rate of about 1-4 nm/min, while treating a silicon dioxide substrate with the same base-water-acid-water process (e.g., the same solution strength, time, and temperature) resulted in an etch rate of about +5 nm/min.

[0073] Applying the ultrasonication process sequences discussed above can provide a predictable etch rate for the substrate materials. Thus, ultrasonication can be used to reduce the dimensions of nano-structures in a controlled and deliberate manner. Due to the substantially uniform reactive environment, the line edge roughness (LERs) can be smooth compared to conventional lithography techniques and precise dimensions can be achieved by tuning one or more ultrasonication conditions. For example, by adjusting the length of time of the ultrasonication bath, the temperature, and/or the solution strength, the amount of material removed may be adjusted. Moreover, because silicon and silicon dioxide are associated with consistent and/or predictable etch rates, the differences in etch rates between these two materials can be leveraged to fabricate multi-tiered structures in a selective and controllable manner.

[0074] FIGS. 6A-6B, 7A-7B, 8A-8B, 9A-9B, and 10A-10B illustrate examples of substrates having a plurality of nano-structures that can be fabricated according to embodiments of this disclosure. Nano-structures fabricated according to embodiments of this disclosure can be used, for example, in one or more gratings for an eyepiece that can be used in a wearable head device (e.g., wearable head device 2102).

[0075] FIG. 6A illustrates an exemplary substrate 600A, according to embodiments of this disclosure. As shown in the figure, substrate 600A can include a base 602A and a plurality of nano-structures 604A. The exemplary substrate 600A may be a silicon substrate. The plurality of nano-structures 604A can form a pattern on the surface of the base 602A. As shown in the figure, the plurality of nano-structures 604A can assume a lines and spaces pattern, such that the nano-structures can protrude from a surface of the base 602A. The pattern geometry is not intended to limit the scope of this disclosure and any suitable nano-pattern, including but not limited to, e.g., a pillars pattern, discontinuous lines, curves, holes, cylinders, etc., can be used without departing from the scope of this disclosure. The plurality of nano-structures 604A may be associated with a first height (600h1) and a first width (600d1). In one or more examples, the nano-structures 604A can have a width (600d1) in a range of about 100-250 nm and a height (600h1) of about 70-150 nm. For example, 604A may have a width 600d1 of 196 nm and height 600h1 of 79 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure.

[0076] FIG. 6B illustrates an exemplary etched substrate 600B that has been etched according to one or more embodiments of this disclosure. For example, substrate 600B may be produced by etching silicon substrate 600A using a base-acid-water ultrasonication process sequence according to one or more examples of this disclosure. As discussed above, a silicon substrate may have an etch rate of about 1-4 nm/min using a base-acid-water sequence. As shown in the figure, the etched nano-structures 604B may have a reduced line width 600d2 compared to the line width 600d1. For example, nano-structures 604B may have a width 600d2 of 145 nm and a height 600h2 of 77 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure. Further, as shown in the figure, the line edge roughness (LER) of the nano-structures 604B can be smooth, particularly when compared to the LER associated with conventional lithography processes at the nano-scale. Comparing the dimensions of nano-structures 604A to nano-structures 604B, the change in the width (600Δd) between 600d1 and 600d2 can be-

51 nm, while the change in height ($600\Delta h$) between $600h1$ and $600h2$ can be about-2 nm. In this manner, the line width dimension d can be reduced to achieve a desired nano-structure geometry, while the height of the nano-structures can remain relatively consistent.

[0077] FIG. 7A illustrates an exemplary substrate **700A**, according to embodiments of this disclosure. As shown in the figure, substrate **700A** can include a base **702A** and a plurality of nano-structures **704A**. The exemplary substrate **700A** may be a silicon dioxide substrate. The plurality of nano-structures **704A** can form a pattern on the surface of the base **702A**. As shown in the figure, the plurality of nano-structures **704A** may be a lines and spaces pattern, such that the nano-structures **704A** can protrude from a surface of the base **702A**. The pattern geometry is not intended to limit the scope of this disclosure and any suitable nano-pattern can be used, as discussed above, without departing from the scope of this disclosure. The plurality of nano-structures **704A** may be associated with a first height ($700h1$) and a first width ($700d1$). In one or more examples, the nano-structures **704A** can have a width ($600d1$) in a range of about 100-250 nm and a height ($600h1$) of about 70-150 nm. For example, **704A** may have a width $700d1$ of 157 nm and height $700h1$ of 122 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure.

[0078] FIG. 7B illustrates an exemplary etched substrate **700B** that can be etched according to one or more embodiments of this disclosure. For example, substrate **700B** may be produced by etching silicon dioxide substrate **700A** using a base-acid-water ultrasonication process sequence according to one or more examples of this disclosure. As discussed above, a silicon dioxide substrate may have an etch rate of about 0.2-0.8 nm/min using a base-acid-water sequence. As shown in the figure, the etched nano-structures **704B** may have a reduced line width $700d2$ compared to the line width $700d1$, and an increased height $700h2$ compared to height $700h1$. For example, nano-structures **704B** may have a width $700d2$ of 141 nm and a height $700h2$ of 125 nm. Comparing the dimensions of nano-structures **704A** to nano-structures **704B**, the change in the width ($700\Delta d1$) between $700d1$ and $700d2$ can be about-16 nm, while the change in height ($700\Delta h1$) between $700h1$ and $700h2$ can be about +3 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure. Similar to the example discussed above, the line width dimension d can be reduced to achieve a desired nano-structure geometry, while the height of the nano-structures **704B** can remain relatively consistent. Further, the LER of the nano-structures **704B** can be smooth, particularly when compared to the LER associated with conventional lithography processes at the nano-scale.

[0079] FIG. 7C illustrates an exemplary etched substrate **700C** that may be etched according to one or more embodiments of this disclosure. For example, substrate **700C** may be produced by etching silicon dioxide substrate **700B** using a base-acid-water ultrasonication process sequence according to one or more examples of this disclosure. Accordingly, multiple sequential ultrasonication processes can be performed to achieve a desired nano-structure geometry. As shown in the figure, the etched substrate **700C** may have a reduced line width $700d3$ compared to the line width $700d2$, and an increased height $700h3$ compared to height $700h2$. For example, **704C** may have a width $700d3$ of 125 nm and a height $700h3$ of 124 nm. Comparing the dimensions of nano-structures **704C** to nano-structures **704C**, the change in the width ($700\Delta d2$) between $700d2$ and $700d3$ may be about-16 nm, while the change in height ($700\Delta h2$) between $700h1$ and $700h2$ may be about-1 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure. Similar to the examples discussed above, the line width dimension d can be reduced to achieve a desired nano-structure geometry, while the height of the nano-structures can remain relatively consistent. Further the LER of the nano-structures **704C** may be smooth, particularly when compared to the LER associated with conventional lithography processes at the nano-scale.

[0080] FIG. 8A illustrates an exemplary substrate **800A**, according to embodiments of this disclosure. As shown in the figure, substrate **800A** can include a base **802A** and a plurality of nano-

structures **804A**. The exemplary substrate **800A** may be a silicon substrate. The plurality of nano-structures **804A** can form a pattern on the surface of the base **802A**. As shown in the figure, the plurality of nano-structures **804A** may be a lines and spaces pattern that can protrude from a surface of the base **802A**. The pattern geometry is not intended to limit the scope of this disclosure and any suitable nano-pattern can be used, as discussed above, without departing from the scope of this disclosure. The plurality of nano-structures **804A** may be associated with a first height (**800h1**) and a first width (**800d1**). In one or more examples, the nano-structures **804A** can have a width **800d1** in a range of about 100-250 nm and a height **800h1** of about 70-150 nm. For example, **804A** may have a width **800d1** of about 219 nm and height **800h1** of about 115 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure.

[0081] FIG. **8B** illustrates an exemplary etched substrate **800B** that can be etched according to one or more embodiments of this disclosure. For example, substrate **800B** may be produced by etching silicon substrate **800A** using a base-water-acid-water ultrasonication process sequence according to one or more examples of this disclosure. As discussed above, a silicon substrate may have an etch rate of about 1-4 nm/min using a base-water-acid-water sequence. As shown in the figure, the etched nano-structure **804B** may have a reduced line width **800d2** compared to the line width **800d1**, and an increased height **800h2** compared to height **800h1**. For example, nano-structures **804B** may have a width **800d2** of about 114 nm and a height **800h2** of about 114 nm. Comparing the dimensions of nano-structures **804A** to nano-structures **804B**, the change in the width (**800Δd**) between **800d1** and **800d2** can be about -105 nm, while the change in height (**800Δh**) between **800h1** and **800h2** can be about -1 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure. Similar to the example discussed above, the line width dimension d can be reduced to achieve a desired nano-structure geometry, while the height of the nano-structures can remain relatively consistent. Further, as shown in the figure, the LER of the nano-structures **804B** can be smooth, particularly when compared to the LER associated with conventional lithography processes at the nano-scale.

[0082] FIG. **9A** illustrates an exemplary substrate **900A**, according to embodiments of this disclosure. As shown in the figure, substrate **600A** can include a base **902A** and a plurality of nano-structures **904A**. The exemplary substrate **900A** may be a silicon dioxide substrate. The plurality of nano-structures **904A** can form a pattern on the surface of the base **902A**. As shown in the figure, the plurality of nano-structures **904A** may be a lines and spaces pattern that can protrude from a surface of the base **902A**. The pattern geometry is not intended to limit the scope of this disclosure and any suitable nano-pattern can be used, as discussed above, without departing from the scope of this disclosure. The plurality of nano-structures **904A** may be associated with a first height (**900h1**) and a first width (**900d1**). In one or more examples, the nano-structures **904A** can have a width (**900d1**) in a range of about 100-250 nm and a height (**900h1**) of about 70-150 nm. For example, **904A** may have a width, **900d1** of about 125 nm and height, **900h1** of about 123 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure.

[0083] FIG. **9B** illustrates an exemplary etched substrate **900B** that can be etched according to one or more embodiments of this disclosure. For example, substrate **900B** may be produced by etching silicon dioxide substrate **900A** using a base-acid-water ultrasonication process sequence according to one or more examples of this disclosure. As discussed above, a silicon dioxide substrate may have an etch rate of about 0 nm/min using a base-water-acid-water sequence. As shown in the figure, the etched nano-structures **904B** may have about the same dimensions as nano-structures **904A**. For example, nano-structures **904B** may have a width **900d2** of about 125 nm and a height **900h2** of about 123 nm. Comparing the dimensions of nano-structures **604A** to nano-structures **604B**, the change in the width (**900Δd**) between **900d1** and **900d2** can be about 0 nm, while the change in height (**900Δh**) between **900h1** and **900h2** can be about 0 nm. These exemplary

dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure. In some examples, the LER of the nano-structures **904B** can be smoother than the LER of nano-structures **904A**.

[0084] FIG. **10A** illustrates an exemplary substrate **1000A**, according to embodiments of this disclosure. As shown in the figure, substrate **600A** can include a base **1002A** and a plurality of nano-structures **1004A**. The exemplary substrate **1000A** may be a silicon substrate. The plurality of nano-structures **1004A** can form a pattern on the surface of the base **1002A**. As shown in the figure, the plurality of nano-structures **1004A** may be a lines and spaces pattern that can protrude from a surface of the base **1002A**. The pattern geometry is not intended to limit the scope of this disclosure and any suitable nano-pattern can be used, as discussed above, without departing from the scope of this disclosure. The plurality of nano-structures **1004A** may be associated with a first height **1000h1** and a first width **1000d1**. In one or more examples, the nano-structures **1004A** can have a width **1000d1** in a range of about 100-250 nm and a height **1000h1** in a range of about 70-150 nm. For example, **1004A** may have a width **1000d1** of about 126 nm and height **1000h1** of about 130 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure.

[0085] FIG. **10B** illustrates an exemplary etched substrate **1000B** that can be etched according to one or more embodiments of this disclosure. For example, substrate **1000B** may be produced by etching silicon substrate **1000A** using a base-water-acid-water ultrasonication process sequence according to one or more examples of this disclosure. As discussed above, a silicon substrate may have an etch rate of about 1-4 nm/min using a base-acid-water sequence. As shown in the figure, the etched substrate **1000B** may have a reduced line width **1000d2** compared to the line width **1000d1**, while the height can remain about the same (e.g., +5 nm). For example, **1004B** may have a width **1000d2** of about 47 nm and a height **1000h2** of about 125 nm. Comparing the dimensions of nano-structures **1004A** to nano-structures **1004B**, the change in the width between **1000d1** and **1000d2** can be about -79 nm, while the change in height between **1000h1** and **1000h2** can be about -5 nm. These exemplary dimensions are provided for illustrative purposes and not intended to limit the scope of the disclosure. Similar to the example discussed above, the line width dimension d can be reduced to achieve a desired nano-structure geometry, while the height of the nano-structures can remain relatively consistent. Further, the LER of the nano-structures **1004B** can be smooth, particularly when compared to the LER associated with conventional lithography processes at the nano-scale. While substrate **1000B** was produced using a similar process sequence to substrate **800B**, in some examples, the thinner line widths of substrate **1000B** may be due to a change in one or more ultrasonication conditions, e.g., length of time exposed to ultrasonication, temperature of liquid bath, concentration of acid and/or base solution, etc.

Exemplary Multi-Tiered Nano-Patterns

[0086] As discussed above, different substrate materials (e.g., silicon and silicon dioxide) can be associated with consistent and/or predictable etch rates. Moreover, varying the ultrasonication process sequences (e.g., base-acid-water (B-A-W), base-water-acid-water (B-W-A-W)) may provide different relative etch rates between the substrate materials. Thus, the differences in etch rates between these two materials can be leveraged to fabricate multi-tiered structures in a selective and controllable manner. For example, by adjusting the ultrasonication conditions, e.g., length of time of the ultrasonication bath, temperature, solution strength, and/or process sequence, the amount of material removed may be predetermined and/or controlled. Thus, multi-tiered nano-structures with a varying cross-sectional geometry can be achieved by exposing a substrate to a single set of ultrasonication conditions. In some embodiments, various geometries, including, but not limited to stepped, re-entrant, and blazed can be achieved using fabrication processes according to embodiments of this disclosure.

[0087] FIGS. **11A-11C**, **12A-12C**, and **13A-13E** illustrate exemplary multi-tiered substrates at various stages in the ultrasonication fabrication process according to embodiments of this

disclosure. For example, FIGS. **11B** and **11C** illustrate exemplary substrates with a stepped geometry, fabricated according to embodiments of this disclosure. FIGS. **12B** and **12C** illustrate exemplary substrates with a re-entrant geometry, fabricated according to embodiments of this disclosure. FIG. **13E** illustrates an exemplary substrate with a blazed geometry, fabricated according to embodiments of this disclosure. The exemplary multi-tiered structures can be formed from one or more layers of silicon-based materials, including for example, but not limited to silicon, silicon dioxide, silicon nitride, and/or other silicon-based materials. As shown in the figures, and discussed in greater detail below, the grating geometry, e.g., stepped geometry, re-entrant geometry, and blazed geometry, can be achieved by leveraging the different etch rates of the different materials.

[0088] FIGS. **11A-11C** illustrate exemplary multi-tiered substrates at various stages in ultrasonication fabrication processes according to embodiments of this disclosure. For example, FIG. **11A** illustrates multi-tiered substrate **1100A** prior to the ultrasonication process. As shown in the figure, the multi-tiered substrate **1100A** can include a base **1102A** and a plurality of nano-structures **1104A**. Each of the plurality of nano-structures **1104A** can include a first layer **1106A** disposed on the base **1102A** and a second layer **1108A** disposed on the first layer **1106A**. As shown in the figure, both the first layer **1106A** and the second layer **1108A** can have the same width. In some embodiments, the base **1102A** and the first layer **1106A** can be formed from silicon dioxide, and the second layer **1108A** can be formed from silicon. In some embodiments, the first and second layers can be deposited using lithography techniques.

[0089] As discussed above, silicon and silicon dioxide can be associated with different etch rates. For example, silicon can be associated with a greater etch rate than silicon dioxide. For instance, as discussed above, a base-water-acid-water process sequence may provide an etch rate of about 1-4 nm for silicon and an etch rate of about 0 nm for silicon dioxide. Thus, with reference to substrate **1100A**, using silicon dioxide for the base **1102A** and first layer **1106A** and silicon for the second layer **1108A**, may result in a stepped geometry due to the relatively high etch rate of silicon compared to silicon dioxide.

[0090] FIG. **11B** illustrates stepped substrate **1100B**, fabricated according to embodiments of this disclosure by, for example, applying a base-water-acid-water process sequence to substrate **1100A**. As shown in the figure, the stepped substrate **1100B** can include a base **1102B** and a plurality of nano-structures **1104B**. Each nano-structure **1104B** can include a first layer **1106B** of silicon dioxide and a second layer **1108B** of silicon. As shown in the figure, substrate **1100B** can have a stepped geometry where a width or diameter of the second layer **1108B** can be different from a width or diameter of the first layer **1106B**. This difference in the widths between the first layer **1106B** and the second layer **1108B** can be attributed to the relative differences in etch rates of silicon and silicon dioxide during the ultrasonication process sequence. For instance, as discussed above, a base-water-acid-water process sequence may provide an etch rate of about 1-4 nm for silicon and an etch rate of about 0 nm for silicon dioxide. These exemplary etch rates are consistent with the geometry of substrate **1100B** compared to substrate **1100A**, where the second layer **1108B**, has a smaller width than second layer **110A**; and the base **1102B** and first layer **1106B** have dimensions that are about the same as base **1102A** and first layer **1106A**.

[0091] FIG. **11C** illustrates stepped substrate **1100C**, fabricated according to embodiments of this disclosure by, for example, applying a base-acid-water process sequence to substrate **1100A**. As illustrated in FIG. **11C**, the substrate **1100C** can include a base **1102C** of silicon dioxide and one or more nano-structures **1104C**. Each nano-structure **1104C** can include a first layer **1106C** of silicon dioxide and a second layer **1108B** of silicon. As shown in the figure, substrate **1100C** can have a stepped geometry where a width or diameter of the second layer **1108C** can be different from a width of the first layer **1106C**. This difference in the widths between the first layer **1106B** and the second layer **1108C** can be attributed to the relative differences in etch rates of silicon and silicon dioxide during the ultrasonication process sequence. For instance, as discussed above, a base-acid-

water process sequence may provide an etch rate of about 1-4 nm for silicon and an etch rate of about 0.2-0.7 nm for silicon dioxide. These exemplary etch rates are consistent with the geometry of substrate **1100C** compared to substrate **1100A**, where the second layer **1108C**, has a smaller width than second layer **1108A**; the base **1102C** has a smaller height than base **1102A**; and the first layer **1106C** as a smaller width than first layer **1106A**.

[0092] Additionally, referring to both substrates **1100B** and **1100C**, because ultrasonication provides a substantially uniform reactive environment across the surface of the substrate, the stepped nano-structures **1104C** can be centered, for example, such that each of the nano-structures **1104C** can have a symmetric cross-section. Such alignment of nano-structures using conventional lithography techniques, in comparison, can be difficult and expensive to achieve due to the nano-scale of the structures.

[0093] As discussed above, substrates **1100B** and **1100C** are illustrative of the impact of applying different process sequences to a template substrate. A comparison of exemplary substrates **1100B** and **1100C** illustrates this difference. For instance, silicon dioxide is associated with a higher etch rate for the base-acid-water-process sequence applied to substrate **1100C**, than the base-water-acid-water process sequence applied to substrate **1100B**. Thus, as shown in the figures, first layer **1106C** can have a smaller width than first layer **1106B**. Similarly, the height associated with the base **1102C** can be shorter than the height associated with base **1102B**. Accordingly, different process sequences can be used to achieve different etched substrate geometries and dimensions.

[0094] FIGS. **12A-12C** illustrate exemplary multi-tiered substrates at various stages in ultrasonication fabrication processes according to embodiments of this disclosure. FIG. **12A** illustrates multi-tiered substrate **1200A** prior to the ultrasonication process. As shown in the figure, the multi-tiered substrate **1200A** can include a base **1202A** and a plurality of nano-structures **1204A**. Each of the plurality of nano-structures **1204A** can include a first layer **1206A** disposed on the base **1202A** and a second layer **1208A** disposed on the first layer **1206A**. As shown in the figure, both the first layer **1206A** and the second layer **1208A** can have the same width. In some embodiments, the base **1202A** and the second layer **1208A** can be formed from silicon, and the first layer **1206A** can be formed from silicon dioxide.

[0095] As discussed above, silicon and silicon dioxide can be associated with different etch rates. For example, silicon can be associated with a greater etch rate than silicon dioxide. Thus, with reference to substrate **1200A**, using silicon for the base **1202A** and second layer **1208A** and silicon dioxide for the first layer **1206A**, may result in a re-entrant geometry due to the relatively high etch rate of silicon compared to silicon dioxide. Nano-structures having a re-entrant geometry can be used in light trapping applications such as in color selective waveguides and/or solar cells.

[0096] FIG. **12B** illustrates a re-entrant substrate **1200B**, fabricated according to embodiments of this disclosure by, for example, applying a base-water-acid-water process sequence to substrate **1200A**. As shown in the figure, the stepped substrate **1200B** can include a base **1202B** and a plurality of nano-structures **1204B**. Each nano-structure **1204B** can include a first layer **1206B** of silicon, a second layer **1208B** of silicon dioxide, and a third layer **1210B** of silicon. As shown in the figure, the third layer **1210B**, may disposed on the base **1202B**, the first layer **1206B** can be disposed on the third layer **1210B**, and the second layer **1208B** can be disposed on the first layer. As shown in the figure, substrate **1200B** can have a re-entrant geometry where a width for each layer, e.g., the first layer **1206B**, second layer **1208B**, and third layer **1210B**, can differ. For example, the first layer **1206B** can be wider than the second and third layers **1208B**, **1210B**. In some examples, the third layer **1210B** can be wider than the second layer **1208B**.

[0097] The difference between the widths of the first layer **1206B**, second layer **1208B**, and third layer **1210B** can be attributed to the relative differences in etch rates of silicon and silicon dioxide during the ultrasonication process sequence. For instance, as discussed above, a base-water-acid-water process sequence may provide an etch rate of about 1-4 nm for silicon and an etch rate of about 0 nm for silicon dioxide. These exemplary etch rates are consistent with the geometry of

substrate **1200B** compared to substrate **1200A**. For example, the silicon dioxide first layer **1206B** may have dimensions that are about the same as first layer **1206A**. In contrast, the silicon second layer **1208A** can have a smaller width than second layer **1208A**. Moreover, the silicon third layer **1210B** can be etched from the base **1202A**. For instance, during the etching process sequence material can be removed from the silicon base **1202A** and form the third layer **1210B** beneath the first layer **1206A**. Accordingly, base **1202B** can be shorter than base **1202A**.

[0098] FIG. **12C** illustrates a re-entrant substrate **1200C**, fabricated according to embodiments of this disclosure by, for example, applying a base-acid-water process sequence to substrate **1200A**. As illustrated in FIG. **12C**, the substrate **1200C** can include a base **1202C** of silicon and one or more nano-structures **1204C**. Each nano-structure **1204C** can include a first layer **1206C** of silicon, a second layer **1208C** of silicon dioxide, and a third layer **1210C** of silicon. As shown in the figure, the third layer **1210C**, may disposed on the base **1202C**, the first layer **1206C** can be disposed on the third layer **1210C**, and the second layer **1208C** can be disposed on the first layer. As shown in the figure, substrate **1200C** can have a re-entrant geometry where a width for each layer, e.g., the first layer **1206C**, second layer **1208C**, and third layer **1210C**, can differ. For example, the first layer **1206C** can be wider than the second and third layers **1208C**, **1210C**. In some examples, the third layer **1210C** can be wider than the second layer **1208C**.

[0099] The difference between the widths of the first layer **1206C**, second layer **1208C**, and third layer **1210C** can be attributed to the relative differences in etch rates of silicon and silicon dioxide during the ultrasonication process sequence. For instance, as discussed above, a base-acid-water process sequence may provide an etch rate of about 1-4 nm for silicon and an etch rate of about 0.2-0.7 nm for silicon dioxide. These exemplary etch rates are consistent with the geometry of substrate **1200C** compared to substrates **1200A** and **1200C**. For example, each of the first and second layers **1206C** and **1208C** can have a smaller width than the first and second layers **1206A** and **1208A**. Moreover, the silicon dioxide first layer **1206C** may have dimensions, e.g., width and height, that are smaller than first layer **1206B**. As discussed above with respect to third layer **1210B**, the silicon third layer **1210C** can be etched from the base **1202A**. For instance, during the etching process sequence material can be removed from the silicon base **1202A** and form the third layer **1210C** beneath the first layer **1206A**. Accordingly, base **1202C** can be shorter than base **1202A**.

[0100] Additionally, referring to both substrates **1200B** and **1200C**, because ultrasonication provides a substantially uniform reactive environment across the surface of the substrate, the stepped nano-structures **1204C** can be centered, for example, such that each of the nano-structures **1204C** can have a symmetric cross-section. Such centering of nano-structures using conventional lithography techniques, in comparison, can be difficult and expensive to achieve due to the scale of the structures. Further, ultrasonication can provide a smooth LER and reduce the incidence of line-breaks compared to conventional lithography techniques.

[0101] As discussed above, substrates **1200B** and **1200C** are illustrative of the impact of applying different process sequences to a template substrate. For instance, silicon dioxide is associated with a higher etch rate for the base-acid-water-process sequence applied to substrate **1200C**, than the base-water-acid-water process sequence applied to substrate **1200B**. Thus, as shown in the figures, first layer **1206C** can have a smaller width than first layer **1206B**. Similarly, the height associated with the base **1202C** can be shorter than the height associated with base **1202B**. Accordingly, different process sequences can be used to achieve different etched substrate geometries and dimensions.

[0102] FIGS. **13A-13E** illustrate exemplary multi-tiered substrates at various stages during an ultrasonication fabrication process according to embodiments of this disclosure. FIG. **13A** illustrates multi-tiered substrate **1300A** prior to the ultrasonication process. As shown in the figure, the multi-tiered substrate **1300A** can include a base **1302A** and a plurality of nano-structures **1304A**. Each of the plurality of nano-structures **1304A** can include a first layer **1306A** disposed on

the base **1302A** and a second layer **1308A** disposed on the first layer **1306A**. As shown in the figure, both the first layer **1306A** and the second layer **1308A** can have the same width. In some embodiments, the base **1302A** and the first layer **1306A** can be formed from silicon dioxide, and the second layer **1108A** can be formed from silicon. As discussed above, silicon and silicon dioxide can be associated with different etch rates. For example, silicon can be associated with a greater etch rate than silicon dioxide. Thus, with reference to substrate **1300A**, using silicon dioxide for the base **1302A** and first layer **1306A** and silicon for the second layer **1308A**, may result in a the first layer having a lower etch rate than the second layer.

[0103] FIG. **13E** illustrates an exemplary substrate **1300E** with a blazed geometry, fabricated according to embodiments of this disclosure. In one or more embodiments, substrate **1300E** can be fabricated with the ultrasonication sequence processes according to examples of this disclosure, e.g., a base-water-acid-water sequence process and/or a base-acid-water sequence process. As shown in the figure, the blazed geometry can include a first layer **1306E** disposed on a base **1302E** and a second layer **1308E** disposed on the first layer **1306E**. For example, the first layer can be formed from silicon dioxide and the second layer can be formed from silicon. As shown in the figure, while the first layer **1306E** may be wider than the second layer **1308E**, at least one side of the first layer **1306E** and the second layer **1308E** can be aligned to form the asymmetric blazed structure.

[0104] FIGS. **13B-13D** illustrate exemplary substrates **1300B-1300D**, demonstrating the intermediate steps during the fabrication of substrate **1300E**. As shown in these figures, a mask **1312B-1312D** can be disposed on one or more surfaces of the substrate. The mask **1312B-1312D** can be formed from a material that is not reactive with the acid and base solutions used during the ultrasonication sequence processes. In some embodiments, the mask can be a chrome mask, but other materials can be used without departing from the scope of this disclosure. Accordingly, during ultrasonication, masked substrate surfaces may not be etched, while masked substrate surfaces can be etched to produce the asymmetric blazed geometry.

Exemplary Ultrasonication Process Sequences

[0105] FIG. **14** illustrates an example block diagram directed to a process **1400** for fabricating a multi-tiered structure according to embodiments of this disclosure. For example, process **1400** can be directed to the steps for fabricating the multi-tiered substrates, e.g., substrates **1100B**, **1200B**, and **1300D**, using a base-water-acid-water process sequence. While the following steps associated with process **1400** may be described with respect to FIGS. **11A-11B**, this is not intended to be limiting and this process can be associated with other substrates, e.g., **600B**, **700B**, **700C**.

[0106] In one or more embodiments, a substrate, e.g., substrate **1100A**, can be deposited and submerged in a bath, e.g., liquid bath **506**, of a base solution and sound waves can be applied to the bath to perform ultrasonication (step **1402**). For example, a transducer, e.g., **502**, can be applied to the bath, e.g., **506**, to perform ultrasonication. As discussed above, the base solution can react with a surface of the substrate. Additionally, the applied sound waves can agitate the base solution such that reacted molecules can be continually removed and the surface of the substrate can be continually replenished with unreacted base solution. In one or more examples, submerging the substrate in the base solution can prime the substrate surface for reacting with subsequent solutions, e.g., the acid solution, but not result in removal of material, e.g., a reduction of dimensions of one or more nano-structures. For example, the base solution can lower the energy barrier and weaken bonds between molecules located at or near the substrate surface. In some embodiments, after a predetermined amount of time, the substrate can be removed from the bath of the base solution (step **1404**). The amount of time can be based on, for example, a desired geometry for the fabricated structure and the etch rates of the substrate material for given ultrasonication conditions, e.g., temperature, base solution concentration, etc.

[0107] In some embodiments, the substrate can be submerged in a bath of water and ultrasonication can be applied to the bath (step **1406**). As discussed above, the water can react with the silicon and

silicon dioxide present at the surface of the substrate. As discussed above, the ultrasonication of the water bath can continually provide a reactive environment at the surface of the substrate. In some embodiments, after a predetermined amount of time, the substrate can be removed from the water bath (step **1408**). In some embodiments, the amount of time can be based on, for example, a desired geometry for the fabricated structure and the etch rates of the substrate material for given ultrasonication conditions, e.g., temperature, acid and base solution concentration, etc.

[0108] In some embodiments, the substrate can be submerged in a bath of an acid solution and ultrasonication can be applied to the bath (step **1410**). In some embodiments, the acid solution can react with the silicon and silicon dioxide present at the surface of the substrate such that a predetermined volume of material can be removed based on a length of time ultrasonication is applied to the substrate. As discussed above, the ultrasonication of the water bath can continually provide a reactive environment at the surface of the substrate. In some embodiments, after a predetermined amount of time, the substrate can be removed from the bath of the acid solution (step **1412**). In some embodiments, the volume of material removed can be based on one or more ultrasonication conditions including, but not limited to, the temperature, acid and base solution concentration, and time exposed to the solution. In some embodiments, the amount of time can be based on, for example, a desired geometry for the fabricated structure and the etch rates of the substrate material for given ultrasonication conditions, e.g., temperature, acid solution concentration, etc.

[0109] In some embodiments, the substrate can be submerged in a bath of water and ultrasonication can be applied to the bath (step **1414**). In some examples, the water can remove reactant, residue, and/or debris from the surface of the substrate. In some examples, the water can provide a clean surface free from reactants. As discussed, the ultrasonication of the water bath can continually provide a reactive environment at the surface of the substrate. In some embodiments, after a predetermined amount of time, the substrate can be removed from the water bath (step **1416**). In some embodiments, the substrate removed from the bath at step **1416** can correspond to substrate **600B**, **700B**, **700C**, **1100B**, **1200B**, and/or substrate **1300D**.

[0110] FIG. **15** illustrates an example block diagram directed to a process **1500** for fabricating a multi-tiered structure according to embodiments of this disclosure. For example, process **1500** can be directed to the steps for fabricating the multi-tiered substrates, e.g., substrates **1100C**, **1200C**, and **1300D**, using a base-acid-water process sequence. While the following steps associated with process **1500** may be described with respect to FIGS. **11A** and **11C**, this is not intended to be limiting and this process can be associated with other substrates, e.g., **800B**, **900B**, **1000B**, **1200C** and **1300D**.

[0111] In one or more embodiments, a substrate, e.g., substrate **1100A**, can be submerged in a bath, e.g., liquid bath **506**, of a base solution and sound waves can be applied to the bath to perform ultrasonication (step **1502**). Step **1502** may be similar to step **1402** described above. In some embodiments, after a predetermined amount of time, the substrate can be removed from the bath of the base solution (step **1504**). The amount of time can be based on, for example, a desired geometry for the fabricated structure and the etch rates of the substrate material for given ultrasonication conditions, e.g., temperature, base solution concentration, etc.

[0112] In some embodiments, the substrate can be submerged in a bath of an acid solution and ultrasonication can be applied to the bath (step **1506**). Step **1506** may be similar to step **1410** described above. In some embodiments, after a predetermined amount of time, the substrate can be removed from the bath of the acid solution (step **1508**). In some embodiments, the amount of time can be based on, for example, a desired geometry for the fabricated structure and the etch rates of the substrate material for given ultrasonication conditions, e.g., temperature, acid solution concentration, etc.

[0113] In some embodiments, the substrate can be submerged in a bath of water and ultrasonication can be applied to the bath (step **1510**). Step **1510** may be similar to step **1414** described above. In

some embodiments, after a predetermined amount of time, the substrate can be removed from the water bath (step **1512**). In some embodiments, the substrate removed from the bath at step **1412** can correspond to substrate **1100C**, substrate **1200C**, and/or substrate **1300D**.

[0114] Accordingly, ultrasonication process sequences can be used to etch substrates to form nano-structures suitable for optical gratings according to embodiments of this disclosure. Such ultrasonication techniques can reduce one or more dimensions of an initial substrate in a controlled manner, e.g., based on known etch rates for different materials to achieve a desired geometry and/or dimensions for one or more nano-structures. Moreover, because ultrasonication can provide a substantially uniform reactive environment across the surface of the substrate, the stepped nano-structures **1104C** can be centered, for example, such that each of the nano-structures **1104C** can have a symmetric cross-section. Such alignment of nano-structures using conventional lithography techniques, in comparison, can be difficult and expensive to achieve due to the scale of the structures. Finally the ultrasonication sequence processes according to embodiments of this disclosure can provide smooth LER without line breaks.

[0115] Embodiments according to this disclosure can also provide methods for fabricating substrates with asymmetric cross-sectional geometries. For example, FIG. **16** illustrates an example block diagram directed to a process **1600** for fabricating a multi-tiered structures, e.g., multi-tiered blazed structures, according to embodiments of this disclosure. For example, process **1600** can be directed to the steps for fabricating a blazed multi-tiered substrates, e.g., **1300E**.

[0116] In one or more embodiments, a mask can be applied to one or more surfaces of a substrate (step **1602**). For example, FIG. **13B** illustrates an exemplary substrate **1300B** where a mask **1312B** has been applied to a surface of the substrate. As shown in the figure, the mask can be applied at an angle such that one or more surfaces of the substrate **1300B**, but not all of the surfaces, have a mask **1312B** disposed thereon. In some examples, the mask can include a glancing angle deposition (GLAD) mask and/or protective material using physical vapor deposition such a E-beam. The E-beam process can evaporate one or more metal or inorganic material, e.g., chrome (Cr), titanium (Ti), nickel (Ni), silicon dioxide (SiO₂), titanium dioxide (TiO₂), aluminum oxide (Al₂O₃), etc., to ensure stable adhesion of the deposited material to the coated surface. During the GLAD process the substrate can be angled with respect to the source of the mask material, thereby creating a shadow in the deposition path over the nano-pattern on the surface of the substrate. In one or more embodiments, the mask can be a chrome mask. In one or more embodiments, the mask can be formed from a material that is resistant to the selected acid and base solutions used during the ultrasonication process sequences described above.

[0117] In one or more embodiments, one or more portions of the mask can be removed (step **1604**). For example, FIG. **13C** illustrates an exemplary substrate **1300C** where one or more portions of a mask has been removed such that mask **1312C** remains on the surface of the substrate. The one or more portions of a mask, e.g., mask **1312B** can be removed via a dry etching process. For example, plasma and/or reactive gases such as fluorocarbons, oxygen, chlorine, and/or boron trichloride can be used to remove portions of the mask. In some examples, the dry etching can be antistrophic such that portions of the mask disposed on horizontal substrate surfaces are removed, while portions of the mask on vertical substrate surfaces remain. In some examples, other antistrophic mask removing processes can be used. As shown in the figure, following step **1604**, the remaining mask **1312C** can be disposed along the right vertical side of nano-structure **1304C**.

[0118] In one or more embodiments, the ultrasonication processes described above, e.g., ultrasonication process **1400** and/or ultrasonication process **1500** can be applied to the substrate (step **1606**). For instance, a base-water-acid-water ultrasonication process and/or a base-acid-water ultrasonication process can be applied to the substrate, e.g., substrate **1300C**. FIG. **13D** illustrates an exemplary substrate **1300D**, after the ultrasonication process has been applied. As shown in the figure, the ultrasonication process can remove material from one or more layers of the nano-structures **1304D**. For example, material can be removed from the silicon second layer **1308D**. As

shown in the figure, the mask **1312D** disposed along the right edge of the nano-structure **1304D** may prevent removal of material from the right edge of the nano-structure **1304D** during ultrasonication. Accordingly, use of the mask **1312D** can prevent removal of material from the masked surface of the substrate during ultrasonication to produce an asymmetric blazed structure. [0119] In one or more embodiments, the remaining mask, e.g., mask **1312D**, can be removed from the substrate, e.g., **1300D** (step **1608**). In some embodiments, the mask can be removed using a wet etching process. For example, the substrate, e.g., substrate **1300D**, can be submerged in a solution configured to etch the mask, e.g., **1312D**, without reacting and/or removing substrate material, e.g., silicon and silicon dioxide. FIG. **13E** illustrates an exemplary blazed substrate **1300E** that can be produced by process **1600**.

[0120] Disclosed herein are systems and methods for fabricating nano-structures on a substrate. The substrate including a plurality of nano-structures can be used in eyepieces for displays, such as for a head wearable device. An example method for fabricating and/or etching a substrate including a plurality of nano-structures for an eyepiece can include submerging the substrate in a bath and applying ultrasonication to the bath for a first time period. The ultrasonication applied to the first bath can agitate the fluid to provide a substantially uniform first reactive environment across the surface of the substrate. Embodiments disclosed herein may provide a robust and easy to manufacture display system that can provide consistent digital image quality during use. The substrate can be submerged in a second bath and ultrasonication can be applied to the second bath for a second time period. The ultrasonication applied to the second bath can agitate the fluid to provide a substantially uniform second reactive environment across the surface of the substrate. In some examples, a predetermined amount of material can be removed from the surface of the substrate during the second time period to produce an etched substrate. In some examples, the predetermined amount of material removed can be based on a length of the first time period and further on a length of the second time period.

[0121] In one or more examples, the process for fabricating nano-structures on a substrate can include depositing a mask onto one or more surfaces of the substrate, and removing one or more portions of the mask from the substrate. In some examples, at least a portion of the surface of the substrate is masked during the etching.

[0122] In one or more examples, the predetermined amount of material can be uniformly removed from the surface of the substrate such that a cross-section of the plurality of nano-structures of the etched substrate can be symmetric. In one or more examples, a thickness of the predetermined amount of material removed from the surface can be in a range of about 5-50 nm.

[0123] In one or more examples, the substrate can include a base comprising a first material. The nano-structures of the plurality of nano-structures can be disposed on the base, the nano-structures can include a first layer. In some examples, the first layer can include a second material, different from the first material. In some examples, the nano-structures can have a substantially uniform width. In some examples, the base can be associated with a first etch rate for a first set of ultrasonication conditions; and the first layer can be associated with a second etch rate for the first set of ultrasonication conditions. In one or more examples, the substrate can be formed from at least one selected from silicon, silicon dioxide, and silicon nitride. In one or more examples, the acid solution can comprise approximately a 2% concentration of sulfuric acid in water. In one or more examples, the base solution comprises approximately a 2% concentration of hydrogen peroxide or potassium hydroxide in water.

[0124] In one or more examples, each nano-structure of the plurality of nano-structures can have a geometry corresponding to one selected from a stepped geometry, a re-entrant geometry, and a blazed geometry. In one or more examples, The ultrasonication conditions can include one or more of a temperature associated with one or more of the first bath and second bath, the length of time associated with the first time period, the length of time associated with the second time period, a concentration of the acid solution, and a concentration of the base solution.

[0125] A compound according to embodiments of this disclosure can include a substrate including a base having a first surface and a plurality of nano-structures disposed on the first surface. In some examples, the substrate can be configured to be etched by applying an ultrasonication process sequence to the substrate to form an etched substrate. In some examples, the etched substrate can include a plurality of etched nano-structures, where the plurality of etched nano-structures can be fabricated by removing a first predetermined amount of material from the first surface and further removing a second predetermined amount of material from one or more surfaces of the plurality of nano-structures.

[0126] In one or more examples, a thickness of the predetermined amount of material removed from the surface of the substrate can be in a range of about 5-50 nm. In one or more examples, the predetermined amount of material can be uniformly removed from the first surface and the one or more surfaces of the plurality of nano-structures such that a cross-section of the plurality of etched nano-structures of the etched substrate can be symmetric.

[0127] In one or more examples, the ultrasonication process sequence can include submerging the substrate in a first bath, where the first bath comprises a first fluid and applying ultrasonication to the first bath for a first time period, where applying ultrasonication agitates the first fluid to provide a substantially uniform first reactive environment across the surface of the substrate. In some examples, the ultrasonication process sequence can include submerging the substrate in a second bath, where the second bath comprises a second fluid, and applying ultrasonication to the second bath for a second time period, where applying ultrasonication agitates the second fluid to provide a substantially uniform second reactive environment across the surface of the substrate. In one or more examples, the predetermined amount of material can be removed during the second time period to produce an etched substrate. In one or more examples, the amount of predetermined amount of material can be based on a length of the first time period and further on a length of the second time period. In one or more examples, The ultrasonication conditions can include one or more of a temperature associated with one or more of the first bath and second bath, the length of time associated with the first time period, the length of time associated with the second time period, a concentration of the acid solution, and a concentration of the base solution.

[0128] In one or more examples, the base of the substrate can comprise a first material and the nano-structure of the plurality of nano-structures can form a first layer, wherein the first layer comprises a second material, different from the first material. In one or more examples, the base can be associated with a first etch rate for a first set of ultrasonication conditions and the first layer can be associated with a second etch rate for the first set of ultrasonication conditions. In one or more examples, the substrate can be formed from at least one selected from silicon, silicon dioxide, and silicon nitride. In one or more examples, the acid solution can comprise approximately a 2% concentration of sulfuric acid in water. In one or more examples, the base solution comprises approximately a 2% concentration of hydrogen peroxide or potassium hydroxide in water.

[0129] In one or more examples, each nano-structure of the plurality of nano-structures has a substantially uniform width. In one or more examples, each etched nano-structure of the plurality of nano-structures can have a geometry corresponding to one selected from a stepped geometry, a re-entrant geometry, and a blazed geometry.

[0130] Although the disclosed examples have been fully described with reference to the accompanying drawings, it is to be noted that various changes and modifications will become apparent to those skilled in the art. For example, elements and/or components illustrated in the drawings may be not be to scale and/or may be emphasized for explanatory purposes. As another example, elements of one or more implementations may be combined, deleted, modified, or supplemented to form further implementations. Other combinations and modifications are to be understood as being included within the scope of the disclosed examples as defined by the appended claims.

Claims

1. A method of etching a substrate including a plurality of nano-structures, the method comprising: submerging the substrate in a first bath, the first bath comprising a first fluid; applying ultrasonication to the first bath for a first time period, wherein applying ultrasonication agitates the first fluid to provide a substantially uniform first reactive environment across a surface of the substrate; submerging the substrate in a second bath, the second bath comprising a second fluid; and applying ultrasonication to the second bath for a second time period, wherein applying ultrasonication agitates the second fluid to provide a substantially uniform second reactive environment across the surface of the substrate, and wherein a predetermined amount of material is removed from the surface of the substrate during the second time period to produce an etched substrate, wherein the amount of material is predetermined based on a length of the first time period and based further on a length of the second time period.
2. The method of claim 1, wherein a thickness of the predetermined amount of material removed from the surface is in a range of 5-50 nm.
3. The method of claim 1, wherein the predetermined amount of material is uniformly removed from the surface of the substrate such that a cross-section of the plurality of nano-structures of the etched substrate is symmetric.
4. The method of claim 1, wherein: the substrate comprises a base comprising a first material; the nano-structures of the plurality of nano-structures are disposed on the base, the nano-structures comprising a first layer, the first layer comprising a second material different from the first material, the nano-structures of the plurality of nano-structures have a substantially uniform width, and the base is associated with a first etch rate for a first set of ultrasonication conditions and the first layer is associated with a second etch rate for the first set of ultrasonication conditions.
5. The method of claim 4, wherein each nano-structure of the plurality of nano-structures has a geometry corresponding to one of a stepped geometry, a re-entrant geometry, and a blazed geometry.
6. The method of claim 4, wherein the ultrasonication conditions of the first set of ultrasonication conditions include one or more of: a temperature associated with one or more of the first bath and the second bath, the length of time associated with the first time period, the length of time associated with the second time period, a concentration of the acid solution, and a concentration of the base solution.
7. The method of claim 1, wherein the substrate is formed from at least one of silicon, silicon dioxide, and silicon nitride.
8. The method of claim 1, wherein the acid solution comprises approximately a 2% concentration of sulfuric acid in water.
9. The method of claim 1, wherein the base solution comprises approximately a 2% concentration of hydrogen peroxide or potassium hydroxide in water.
10. The method of claim 1, further comprising: depositing a mask onto one or more surfaces of the substrate; and removing one or more portions of the mask from the substrate, wherein at least a portion of the surface of the substrate is masked during the second time period.
11. A compound comprising: a substrate comprising: a base comprising a first surface; and a plurality of nano-structures disposed on the first surface, wherein the substrate is configured to be etched by applying an ultrasonication process sequence to the substrate to form an etched substrate, the etched substrate comprising a plurality of etched nano-structures, and wherein the etched nano-structures are fabricated by removing a first predetermined amount of material from the first surface and further by removing a second predetermined amount of material from one or more surfaces of the plurality of nano-structures.
12. The compound of claim 11, wherein a thickness of the predetermined amount of material

removed from the first surface is in a range of 5-50 nm.

13. The compound of claim 11, wherein the predetermined amount of material is uniformly removed from the first surface and further is uniformly removed from the one or more surfaces of the plurality of nano-structures such that a cross-section of the plurality of etched nano-structures of the etched substrate is symmetric.

14. The compound of claim 11, wherein the ultrasonication process sequence comprises: submerging the substrate in a first bath, the first bath comprising a first fluid; applying ultrasonication to the first bath for a first time period, wherein applying ultrasonication agitates the first fluid to provide a substantially uniform first reactive environment across the first surface of the substrate; submerging the substrate in a second bath, the second bath comprising a second fluid; and applying ultrasonication to the second bath for a second time period, wherein applying ultrasonication agitates the second fluid to provide a substantially uniform second reactive environment across the first surface of the substrate, and wherein the predetermined amount of material is removed during the second time period to produce an etched substrate, wherein the amount of material is predetermined based on a length of the first time period and based further on a length of the second time period.

15. The compound of claim 14, wherein: the base comprises a first material, the nano-structures of the plurality of nano-structures comprises a first layer, the first layer comprising a second material different from the first material, the base is associated with a first etch rate for a first set of ultrasonication conditions, and the first layer is associated with a second etch rate for the first set of ultrasonication conditions.

16. The compound of claim 15, wherein each nano-structure of the plurality of nano-structures has a substantially uniform width, and wherein each etched nano-structure of the plurality of nano-structures has a geometry corresponding to one of a stepped geometry, a re-entrant geometry, and a blazed geometry.

17. The compound of claim 15, wherein the ultrasonication conditions of the first set of ultrasonication conditions include one or more of: a temperature associated with one or more of the first bath and second bath the length of time associated with the first time period, the length of time associated with the second time period, a concentration of the acid solution, and a concentration of the base solution.

18. The compound of claim 14, wherein the acid solution comprises approximately a 2% concentration of sulfuric acid in water.

19. The compound of claim 14, wherein the base solution comprises approximately a 2% concentration of hydrogen peroxide or potassium hydroxide in water.

20. The compound of claim 11, wherein the substrate is formed from at least one of silicon, silicon dioxide, and silicon nitride.
