

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12402457
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Qin; Xuefei

Light-emitting panel, method for fabricating the light-emitting panel, and display device

Abstract

A light-emitting panel, a method for fabricating a light-emitting panel, and a display device are provided in embodiments of the present application. The light-emitting panel includes: a substrate, and a plurality of light-emitting elements, a reflective layer and a protective layer that are disposed at a side of the substrate, wherein the reflective layer is located between the substrate and the protective layer; and wherein both the protective layer and the reflective layer are provided with openings, the substrate includes bonding points within the openings, and the light-emitting elements are electrically connected to the bonding points.

Inventors: Qin; Xuefei (Shanghai, CN)

Applicant: Shanghai Tianma Microelectronics Co., Ltd. (Shanghai, CN)

Family ID: 1000008780364

Assignee: SHANGHAI TIANMA MICROELECTRONICS CO., LTD. (Shanghai, CN)

Appl. No.: 17/721385

Filed: April 15, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230246145 A1	Aug. 03, 2023

Foreign Application Priority Data

CN	202210111537.X	Jan. 29, 2022
----	----------------	---------------

Publication Classification

Int. Cl.: H10H20/856 (20250101); H01L25/075 (20060101); H10H20/01 (20250101)

U.S. Cl.:

CPC H10H20/856 (20250101); H01L25/0753 (20130101); H10H20/0363 (20250101)

Field of Classification Search

CPC: H10H (20/856); H10H (20/84); H10H (29/842); H10K (50/856); H10K (50/84); H05B (33/24)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2017/0338388	12/2016	Wu	N/A	H10H 20/8506

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
110370770	12/2018	CN	N/A
102125313	12/2019	KR	N/A

Primary Examiner: Movva; Amar

Attorney, Agent or Firm: East IP P.C.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) The present application is based upon and claims priority to Chinese Patent Application No. 202210111537.X, filed on Jan. 29, 2022, which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

(2) The present application relates to the field of display technology, and in particular to a light-emitting panel, a method for fabricating the light-emitting panel, and a display device.

BACKGROUND

(3) With development of display technology, there are more and more types of light-emitting panels. For example, the light-emitting panels may include a light-emitting diode (LED) light-emitting panel, a sub-millimeter light-emitting diode (Mini LED) light-emitting panel, and a micro light-emitting diode (Micro LED) light-emitting panel, and the like.

(4) In order to improve a light-outputting effect of a light-emitting panel, generally a reflective layer with a higher reflectivity, such as white reflective ink, may be applied on a surface of a substrate in the light-emitting panel to improve the light-outputting effect of the light-emitting panel through reflection by the reflective layer of light emitted by light-emitting elements on the substrate.

(5) However, inventors of the present application have found that the reflective layer at positions of bonding points is prone to yellowing during a bonding process of the light-emitting elements, resulting in a poorer light-outputting effect of the light-emitting panel.

SUMMARY

- (6) The embodiments of the present application provide a light-emitting panel, a method for fabricating the light-emitting panel, and a display device.
- (7) In a first aspect, according to the embodiments of the present application, there is provided a light-emitting panel, including: a substrate, and a plurality of light-emitting elements, a reflective layer and a protective layer that are disposed at a side of the substrate, wherein the reflective layer is located between the substrate and the protective layer; and wherein both the protective layer and the reflective layer are provided with openings, the substrate includes bonding points within the openings, and the light-emitting elements are electrically connected to the bonding points.
- (8) In a second aspect, according to the embodiments of the present application, there is provided a method for fabricating a light-emitting panel, wherein the light-emitting panel includes the light-emitting panel according to the first aspect. The method includes: providing a substrate on which bonding points are provided; forming a reflective layer at a side of the substrate where the bonding points are located; forming a protective layer at a side of the reflective layer that is away from the substrate, and forming openings on both the protective layer and the reflective layer to expose the bonding points; and electrically connecting light-emitting elements to the bonding points.
- (9) In a third aspect, according to the embodiments of the present application, there is provided a display device, including the light-emitting panel according to the first aspect.
-

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) In order to illustrate technical solutions of the embodiments of the present application more clearly, the drawings required for the embodiments of the present application will be briefly described. For a person skilled in the art, other drawings can be obtained from these drawings without any inventive effort.
- (2) FIG. 1 is a schematic top view of a light-emitting panel according to an embodiment of the present application;
- (3) FIG. 2 is a schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along a A-A' direction;
- (4) FIG. 3 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction;
- (5) FIG. 4 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction;
- (6) FIG. 5 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction;
- (7) FIG. 6 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction;
- (8) FIG. 7 is a schematic diagram of a relationship between a thickness of a layer in the protective layer and a reflectivity of the reflective layer;
- (9) FIG. 8 is a schematic diagram of hues of a CIE 1931 standard chromaticity system according to an embodiment of the present application;
- (10) FIG. 9 is a schematic diagram of a color gamut of the CIE 1931 standard chromaticity system according to an embodiment of the present application;
- (11) FIG. 10 is a schematic diagram of a relationship between wavelengths of light, incident angles and the reflectivity of the reflective layer according to an embodiment of the present application;
- (12) FIG. 11 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction;
- (13) FIG. 12 is another schematic diagram of hues of the CIE 1931 standard chromaticity system according to an embodiment of the present application;

- (14) FIG. 13 is another schematic diagram of a color gamut of the CIE 1931 standard chromaticity system according to an embodiment of the present application;
- (15) FIG. 14 is another schematic diagram of a relationship between wavelengths of light, incident angles and the reflectivity of the reflective layer according to an embodiment of the present application;
- (16) FIG. 15 is a schematic cross-sectional view of a light-emitting panel according to an embodiment of the present application;
- (17) FIG. 16 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction;
- (18) FIG. 17 is a schematic flowchart of a method for fabricating a light-emitting panel according to an embodiment of the present application;
- (19) FIG. 18 is a schematic process diagram of a method for fabricating a light-emitting panel according to an embodiment of the present application;
- (20) FIG. 19 is another schematic process diagram of a method for fabricating a light-emitting panel according to an embodiment of the present application;
- (21) FIG. 20 is a schematic top view of a display device according to an embodiment of the present application; and
- (22) FIG. 21 is a schematic cross-sectional view of a display device according to an embodiment of the present application.

DETAILED DESCRIPTION

(23) The features and exemplary embodiments of various aspects of the present application will be described in detail below. In order to make the purposes, technical solutions and advantages of the present application more clear, the present application will be further described in detail below with reference to the accompanying drawings and specific embodiments. It should be understood that the specific embodiments described herein are only intended to explain the present application, but not to limit the present application. It will be apparent to a person skilled in the art that the present application may be practiced without some of these specific details. The following description of the embodiments is merely to provide a better understanding of the present application by illustrating examples of the present application.

(24) It should be noted that relational terms in this document such as first and second are used only to distinguish one entity or operation from another entity or operation, and do not necessarily require or imply such actual relationship or sequence between these entities or operations. Moreover, the terms “comprising”, “including” or any other variation thereof are intended to encompass a non-exclusive inclusion such that a process, method, article or device that includes a list of elements not only includes those elements, but also includes other elements that are not explicitly listed but inherent to such a process, method, article or device. Without further limitation, an element defined by the term “comprising . . .” does not preclude presence of additional elements in a process, method, article or device that includes the element.

(25) It should be understood that the term “and/or” used in this document indicates only an association relationship to describe the associated objects, which indicates that there may be three kinds of relationships, for example, “A and/or B” may indicate three cases, one indicating A along, another indicating B alone and yet another indicating both A and B. In addition, the character “/” in this document generally indicates that the associated objects are in an “or” relationship.

(26) It should be understood that an orientation or positional relationship indicated by the terms “center”, “longitudinal”, “lateral”, “length”, “width”, “thickness”, “upper”, “lower”, “front”, “rear”, “left”, “right”, “vertical”, “horizontal”, “top”, “bottom”, “inside”, “outside”, “clockwise”, “counterclockwise”, etc. is an orientation or positional relationship based on that shown in the drawings, and is only provided for conveniently describing the present application and simplifying the description, rather than indicating or implying that the involved device or element must have a specific orientation and must be constructed and operated in a specific orientation, and therefore

should not be construed as a limitation to the present application.

(27) In the embodiments of the present application, the term “electrically connected” may refer to a direct electrical connection between two components, or may refer to an electrical connection between the two components via one or more other components.

(28) It will be apparent to a person skilled in the art that various modifications and variations of the present application can be made without departing from spirits or scopes of the present application. Accordingly, the present application is intended to cover the modifications and variations of the present application that fall within scopes of corresponding claims (i.e. claimed technical solutions) and their equivalents. It should be noted that implementations according to the embodiments of the present application may be combined with each other as long as there is no contradiction.

(29) Before describing the technical solutions according to the embodiments of the present application, the document first specifically describes problems existing in the related art in order to facilitate understanding of the embodiments of the present application.

(30) As mentioned above, the inventors of the present application have found that there is a problem in the related art that the reflective layer is prone to yellowing and the light-emitting panel has a poorer light-outputting effect.

(31) In order to solve the above-mentioned technical problems, the inventors of the present application has firstly conducted researches and made analyses on root causes of the above-mentioned technical problems. The researches and analyses are provided as follows.

(32) For example, for a Mini LED light-emitting panel and a Micro LED light-emitting panel, it is impossible to use a traditional reflector plate to increase its reflectivity due to a smaller size of a light-emitting element (also known as an LED chip) in the light-emitting panel. Therefore, in order to improve a light-outputting effect of the light-emitting panel, it is general that a reflective layer with a higher reflectivity, such as white reflective ink, may be applied on a surface of a substrate in the light-emitting panel so that the reflective layer is used to reflect light emitted from the light-emitting elements, so as to improve the light-outputting effect of the light-emitting panel.

(33) The white reflective ink is mainly composed of organic dispersant carriers and highly reflective particles. The inventors of the present application have found that during a bonding (such as welding) process of the light-emitting elements or a light-emitting process of the light-emitting elements (e.g. the light-emitting elements maintain light emission with a higher strength for a long time period), a surface of the white reflective ink will be oxidized, and organic components on the surface of the white reflective ink will be destroyed, resulting in yellowing of the surface of the white reflective ink. In this way, color of the surface of the white reflective ink will become darker, and a reflectivity of the surface of the white reflective ink will be reduced, which in turn leads to a poorer light-outputting effect of the light-emitting panel.

(34) In addition, the inventors of the present application have found that due to poorer performance of the reflective layer (e.g. the white reflective ink) in isolating moisture, moisture in the air may easily intrude into the light-emitting elements and the substrate, leading that wirings or electronic devices in the light-emitting element and in the substrates may be easily corroded by moisture.

(35) In view of the above findings from researches conducted by the inventors, the embodiments of the present application provide a light-emitting panel, a method for fabricating a light-emitting panel and a display device, which can at least solve the technical problems in the related art that the reflective layer is prone to yellowing and a light-outputting effect of the light-emitting panel is poorer.

(36) A technical concept of the embodiments of the present application is to provide a protective layer at a side of the reflective layer that is away from the substrate, wherein the protective layer can play an anti-oxidation effect and/or a moisture isolation effect, with which oxidation of the reflective layer in the bonding process of the light-emitting elements and in the light-emitting process of the light-emitting elements can be reduced or even avoided, thereby reducing or even avoiding yellowing of the reflective layer and improving the light-outputting effect of the light-

emitting panel; and in another hand, intrusion of moisture can be prevented as much as possible, thereby reducing or even avoiding corrosion of the wirings and electronic devices in the light-emitting elements and in the substrate.

(37) In the embodiments of the present application, the light-emitting element may include, for example, a micro light-emitting diode Micro LED and a sub-millimeter light-emitting diode Mini LED. Correspondingly, the light-emitting panel may include a Micro LED light-emitting panel and a Mini LED light-emitting panel. Such light-emitting panel can be used for fabricating a self-luminous display panel and can be also used as a backlight panel.

(38) The light-emitting panel according to the embodiments of the present application will be firstly described hereinafter.

(39) Referring to FIG. 1 and FIG. 2 where FIG. 1 is a schematic top view of a light-emitting panel according to an embodiment of the present application and FIG. 2 is a schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along a A-A' direction, a light-emitting panel **10** according to the embodiment of the present application includes a substrate **100**, and a plurality of light-emitting elements **101**, a reflective layer **102** and a protective layer **103** at a side of the substrate **100**. The substrate **100** may include, but is not limited to, a rigid substrate, and the rigid substrate may include, but is not limited to, a glass substrate, a printed circuit board (Printed Circuit Board, PCB) substrate or any other rigid substrate. The inventors of the present application have found that in a case where the substrate **100** is a glass substrate, there is a better feasibility in a practical application to provide the above mentioned layer structures (i.e., the reflective layer **102** and the protective layer **103**) on the glass substrate due to better anti-deformation performance of the glass substrate.

(40) In the embodiment of the present application, the reflective layer **102** may include, but is not limited to, white reflective ink (referred to as white ink), and in addition to the white reflective ink, the reflective layer **102** may be formed by any other material with a higher reflectivity, which is not limited herein. The protective layer **103** may have a single-layer structure or a stacked-layers structure, that is, the protective layer **103** may include merely one layer, or may include a plurality of stacked layers.

(41) Still referring to FIG. 2, in a direction Z perpendicular to a plane where the light-emitting panel is located, the reflective layer **102** is located between the substrate **100** and the protective layer **103**. That is, the protective layer **103** is disposed at a side of the reflective layer **102** that is away from the substrate **100**, so as to protect the reflective layer **102** well. The substrate **100** is provided with bonding points **201** for bonding the light-emitting elements **101**. The protective layer **103** and the reflective layer **102** are provided with openings **k1**, the bonding points **201** are disposed within the openings **k1**, and the light-emitting elements **101** are electrically connected by bonding with the bonding points **201**. It should be understood that the bonding points **201** may only refer to bonding positions of the light-emitting elements **101**, and do not represent physical structures; and alternatively, the bonding points **201** may be pad structures for bonding the light-emitting elements **101**.

(42) In a case where the protective layer **103** includes one layer, the protective layer **103** may be formed of a first material. It is easy to understand that an anti-oxidation capability of the first material may be greater than that of a material of the reflective layer **102** (e.g., the white reflective ink), so that an anti-oxidation capability of the protective layer **103** is greater than that of the reflective layer **102**, and thus the protective layer **103** can play a better anti-oxidation effect. Exemplarily, the first material may include silicon nitride SiN.sub.x which has a better anti-oxidation capability, or the first material may include silicon oxynitride SiN.sub.xO.sub.y which has both a better moisture absorption capability and a better anti-oxidation capability. In a case where the protective layer **103** includes a plurality of layers, the protective layer **103** may be formed of a plurality of materials, and some of the materials may have a better moisture absorption capability (e.g. MgO), and the remaining of the materials may have, for example, a better anti-

oxidation capability (e.g. SiN.sub.x).

(43) In this way, since the protective layer **103** with a better anti-oxidation effect is provided at the side of the reflective layer **102** that is away from the substrate **100**, a surface of the reflective layer **102** (e.g. the white reflective ink) will not be oxidized under protection of the protective layer **103** during a bonding (e.g. welding) process of the light-emitting elements **101** with the bonding points **201** or during a light-emitting process of the light-emitting elements **101** (for example, the light-emitting elements maintains light emission with a higher intensity for a long time period), thereby reducing or even avoiding yellowing of the surface of the reflective layer **102** and improving the light-outputting effect of the light-emitting panel **10**.

(44) In addition, a moisture isolation capability (also known as moisture absorption capability) of the first material may be greater than that of the material of the reflective layer **102** (e.g., the white reflective ink), so that a moisture isolation capability of the protective layer **103** is greater than that of the reflective layer **102**, and thus the protective layer **103** can play a better moisture isolation effect. Exemplarily, the first material may include magnesium oxide MgO which has a better moisture absorption capability, or the first material may include silicon oxynitride SiN.sub.xO.sub.y which has both a better moisture absorption capability and a better anti-oxidation capability. In the case where the protective layer **103** includes a plurality of layers, the protective layer **103** may be formed of a plurality of materials, and some of the materials may have a better moisture absorption capability (e.g., MgO), and the remaining of the materials may have, for example, a better anti-oxidation capability (e.g. SiN.sub.x).

(45) In this way, since the protective layer **103** has a better moisture isolation effect, it can prevent intrusion of moisture as much as possible, thereby reducing or even avoiding corrosion of wirings or electronic devices in the light-emitting element **101** and in the substrate **100**.

(46) It should be noted that it is easy for the above-mentioned exemplary materials for the first material, such as MgO, SiN.sub.x and SiN.sub.xO.sub.y, to form a dense layer structure in a film forming process, and thus an anti-oxidation effect and/or a moisture isolation effect can be attained.

(47) The light-emitting panel **10** according to the embodiment of the present application includes the substrate **100**, and the plurality of light-emitting elements **101**, the reflective layer **102** and the protective layer **103** that are disposed at a side of the substrate **100**, wherein the reflective layer **102** is located between the substrate **100** and the protective layer **103**; and wherein both the protective layer **103** and the reflective layer **102** are provided with the openings **k1**, the substrate **100** includes bonding points **201** within the openings **k1**, and the light-emitting elements **101** are electrically connected to the bonding points **102**. In the present application, by providing the protective layer **103** at the side of the reflective layer **102** that is away from the substrate **100**, the protective layer **103** can play an anti-oxidation effect, which can reduce or even avoid oxidation of the reflective layer **102** in a bonding process of the light-emitting elements **101** and in a light-emitting process of the light-emitting elements **101**, thereby reducing or even avoiding yellowing of the reflective layer **102** and improving the light-outputting effect of the light-emitting panel **10**; and/or the protection layer **103** can plays a moisture isolation effect, which prevents intrusion of moisture as much as possible, thereby reducing or even avoiding corrosion of the wirings and electronic devices in the light-elements **101** and in the substrate **100**.

(48) FIG. 3 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the direction A-A'. As shown in FIG. 3, according to some embodiments of the present application, optionally, the protective layer **103** may cover side faces D of the reflective layer **102** that are close to the bonding points **201**. The side faces D of the reflective layer **102** can be specifically understood as side faces (or surfaces) of the reflective layer **102** that are close to the bonding points **201** in the first direction X.

(49) In this way, since the protective layer **103** covers the side faces D of the reflective layer **102** that are close to the bonding points **201**, the side faces D can be prevented from being exposed to the air, thereby oxidation and yellowing of the side faces D of the reflective layer **102** and areas

adjacent to the side faces D can be prevented, so as to ensure that the light-emitting panel **10** has a better light-outputting effect. In addition, intrusion of moisture through the side faces D can also be prevented, which further reducing or even avoiding corrosion of wirings or electronic device in the light-emitting element **101** and in the substrate **100**.

(50) The inventors of the present application have further found that provision of the protective layer **103** at the side of the reflective layer **102** that is away from the substrate **100** can enable that the light-emitting panel **10** has a better anti-oxidation effect and/or a moisture isolation effect, but may cause a reflectivity of the reflective layer **102** to be greatly reduced. For example, the inventors of the present application have found through a large number of experiments that the reflectivity of the reflective layer **102** (such as the white reflective ink with a thickness of 30 μm) that is actually measured is 83.05% and the reflectivity of the reflective layer **102** (e.g. the white reflective ink with a thickness of 30 μm) that is obtained by a simulation software is 82.52% when the protective layer **103** has not be applied. However, in a case where the protective layer **103** is a single layer of SiN.sub.x (for example, the SiN.sub.x has a thickness of 70 nm), the reflectivity of the reflective layer **102** will be reduced to 58.02%; and in a case where the protective layer **103** is a single layer of MgO (for example, the MgO has a thickness of 70 nm), the reflectivity of the reflective layer **102** will be reduced to 59%. Such a large reduction of the reflectivity of the reflective layer **102** is obviously contrary to an initial intention of providing the reflective layer **102**. Therefore, based on the above findings, the inventors of the present application intends to make the light-emitting panel **10** have a better anti-oxidation effect and/or a moisture isolation effect without reducing the reflectivity of the reflective layer **102** as much as possible.

(51) FIG. 4 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the direction A-A'. As shown in FIG. 4, according to some embodiments of the present application, optionally, the protective layer **103** may include at least one first layer **1031** with a first refractive index and at least one second layer **1032** with a second refractive index in order to make the light-emitting panel **10** have a better anti-oxidation effect and/or a moisture isolation effect on the basis that the reflectivity of the reflective layer **102** is reduced by as little as possible. The first refractive index is different from the second refractive index. Exemplarily, the protective layer **103** may include one first layer **1031** and one second layer **1032**, for example, and alternatively, the protective layer **103** may include two first layers **1031** and one second layer **1032**, or the protective layer **103** may include two first layers **1031** and two second layers **1032**. The number of the first layers **1031** and the number of the second layers **1032** in the protective layer **103** is not limited in the embodiments of the present application.

(52) Taking the protective layer **103** including two first layers **1031** and one second layer **1032** as an example, principles of the embodiments of the present application that the reflectivity of the reflective layer **102** will not be reduced as much as possible will be described below.

(53) Since the refractive index of the first layer **1031** is different from the refractive index of the second layer **1032**, i.e., one of the layers has a higher refractive index and the other of the layers has a lower refractive index, the layer with the higher refractive index and the layer with the lower refractive index form an antireflection film (which is a film that ensures the reflectivity of the reflective layer will not be reduced, but transmittance of the reflective layer will be increased), so that the reflectivity of the reflective layer **102** will be reduced slightly or even improved.

(54) For ease of understanding, it is shown in the following expression for a relationship between the reflectivity and the refractive indexes.

$$(55) \quad R = \left[\frac{n_0 - (n_b / n_1)^{2s} n_b^2 / n_g}{n_0 + (n_b / n_1)^{2s} n_b^2 / n_g} \right]^2 \quad (1)$$

where R represents the reflectivity of the reflective layer **102**, n_0 represents a refractive index of the air, $n_{\text{sub.b}}$ represents the refractive index of the first layer **1031**, $n_{\text{sub.1}}$ represents the refractive index of the second layer **1032**, $n_{\text{sub.g}}$ represents a refractive index of the reflective

layer **102**, and s is a preset coefficient, e.g. $s=8$.

(56) It is assumed that $n_{\text{sub}.0}=1$, $n_{\text{sub}.b}=2$, $n_{\text{sub}.1}=1.8$, $n_{\text{sub}.g}=1.5$, $s=8$, which are substituted into the expression (1) to obtain:

$$(57) R = \left[\frac{1 - (2 / 1.8)^{16} 2^2 / 1.5}{1 + (2 / 1.8)^{16} 2^2 / 1.5} \right]^2 = 75.69\%$$

(58) It can be seen from this that the reflectivity of the reflective layer will be greatly improved, for example, reaching 75.69%, when the antireflection film formed by the layer with a higher refractive index and the layer with a lower refractive index is used compared with when the protective layer **103** includes only the single first layer **1031** or only the single second layer **1032**. Moreover, it is general that the larger the $n_{\text{sub}.b}/n_{\text{sub}.g}$ is or the larger the number of layers in the protective layer **103** is, the higher the reflectivity of the reflective layer **102** is.

(59) In this way, since the protective layer **103** includes the first layer **1031** and the second layer **1032** with different refractive indices, the first layer **1031** and the second layer **1032** form an antireflection film, which enables that the light-emitting panel **10** has a better anti-oxidation effect and/or a better moisture isolation effect while keeping the reflectivity of the reflective layer **102** not being reduced as much as possible.

(60) FIG. 5 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction. As shown in FIG. 5, in some specific embodiments, optionally, the protective layer **103** may include one first layer **1031** and one second layer **1032**. In a direction Z perpendicular to a plane where the light-emitting panel **10** is located, the first layer **1031** is disposed at a side of the second layer **1032** that is away from the substrate **100**, and the second refractive index is greater than the first refractive index. That is, in the direction Z perpendicular to the plane where the light-emitting panel **10** is located, the layer with a higher refractive index (e.g., the second layer **1032**) is closer to the reflective layer **102**.

(61) Such settings are based on the inventors' findings that the reflectivity of the reflective layer **102** will be higher when the layer with a higher refractive index (e.g. the second layer **1032**) is closer to the reflective layer **102** and the layer with a lower refractive index (e.g. the first layer **1031**) is further away from the reflective layer **102** compared with a case where the layer with the lower refractive index (e.g. the first layer **1031**) is closer to the reflective layer **102** and the layer with the higher refractive index (e.g. the second layer **1032**) is further away from the reflective layer **102**. In this way, it can achieve an effect of greatly lowering the reduction of the reflectivity of the reflective layer **102** so as to ensure amounts of light outputted through the protective layer **103** in a case where the protective layer **103** includes only a limited number of the first layers **1031** and the second layers **1032** (i.e., there is a smaller number of the first layers **1031** and the second layers **1032**).

(62) It should be noted that, in the embodiment of the present application, it may be that the layer with the lower refractive index (e.g. the first layer **1031**) is closer to the reflective layer **102**, and the layer with the higher refractive index (e.g. the second layer **1032**) is further away from the reflective layer **102**, which is not limited in the embodiment of the present application.

(63) FIG. 6 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction. As shown in FIG. 6, it differs from the embodiment shown in FIG. 5 that in some other specific embodiments, optionally, the protective layer **103** may include at least two first layers **1031** and at least two second films Layers **1032**. In a direction Z perpendicular to the plane where the light-emitting panel **10** is located, the first layers **1031** and the second layers **1032** may be alternately arranged. It should be noted that although FIG. 6 only schematically shows that the protective layer **103** includes two first layers **1031** and two second layers **1032**, it should be understood that the protective layer **103** may include more than two first layers **1031** and more than two second layers **1032**, which is not limited in the embodiment of the present application.

(64) As mentioned above, it is general that the larger the number of layers in the protective layer **103** is, the higher the reflectivity of the reflective layer **102** is. Therefore, since the protective layer

103 includes a plurality of first layers **1031** and a plurality of second layers **1032**, the reflectivity of the reflective layer **102** will be reduced slightly or even will be improved, so that the light-emitting panel **10** has a better anti-oxidation effect and/or a better moisture isolation effect while keeping the reflectivity of the reflective layer **102** not being reduced as much as possible or even improved.

(65) Still referring to FIG. 6, according to some embodiments of the present application, optionally, in the direction Z perpendicular to the plane where the light-emitting panel **10** is located, the layer in the protective layer **103** that is closest to the substrate **100** is the second layer **1032**, and the second refractive index is greater than the first refractive index. That is, in the direction Z perpendicular to the plane where the light-emitting panel **10** is located, the layer in the protective layer **103** that is closest to the reflective layer **102** is the second layer **1032** with a higher refractive index.

(66) As mentioned above, the inventors have found from researches that the reflectivity of the reflective layer **102** will be higher when the layer with a higher refractive index (e.g. the second layer **1032**) is adjacent to the reflective layer **102** compared with a case where the layer with a lower refractive index (e.g. the first layer **1031**) is adjacent to the reflective layer **102**. In this way, reduction of the reflectivity of the reflective layer **102** will be further lowered, or even the reflectivity of the reflective layer **102** will be improved.

(67) It should be noted that, in the embodiment of the present application, it may be that the layer with a lower refractive index (e.g. the first layer **1031**) is adjacent to the reflective layer **102**, which is not limited in the embodiment of the present application.

(68) According to some embodiments of the present application, optionally, each of the first refractive index and the second refractive index may have a value in a range of 1.4 to 2.0.

(69) The reason why each of the refractive indexes according to the embodiments of the present application is set to a value in the above-mentioned range of 1.4 to 2.0 is that the inventors have found that reduction of the reflectivity of the reflective layer **102** will be little or even the reflectivity of the reflective layer **102** will be improved when each of the first refractive index and the second refractive index is set in the range of 1.4 to 2.0. If a wider range is selected for the refractive indices, e.g. when the first refractive index is 1.0 and the second refractive index is 2.5, it is possible to improve the reflectivity of the reflective layer **102**, but such improvement is very limited, and when the first refractive index and the second refractive index are outside of the range of 1.4 to 2.0, the anti-oxidation capability and/or the moisture isolation capability of the materials of the first layer **1031** and the second layer **1032** will be greatly reduced such that the light-emitting panel **10** cannot play a better anti-oxidation effect and/or a moisture isolation effect. Therefore, the range of 1.4 to 2.0 for the first refractive index and the second refractive index enables that reduction of the reflectivity of the reflective layer **102** will be little, and thus the light-emitting panel **10** has a better anti-oxidation effect and/or a better moisture isolation effect.

(70) It should be noted that when each of the first refractive index and the second refractive index is set to a value in the range of 1.4 to 2.0, it is necessary to ensure that the first refractive index is different from the second refractive index, for example, it may be that the first refractive index is smaller than the second refractive index. A difference between the first refractive index and the second refractive index may be flexibly adjusted according to an actual situation, which is not limited in the embodiment of the present application.

(71) The inventors of the present application have further found that a change in a thickness of a layer in the protective layer **103** plays a key role in a magnitude of the reflectivity of the reflective layer **102**. If the first layer **1031** and the second layer **1032** are simply stacked on the reflective layer **102** without considering the thicknesses of the first layer **1031** and the second layer **1032**, the reflectivity of the reflective layer **102** may still be greatly reduced, and thus it is difficult to achieve the effect that reduction of the reflectivity of the reflective layer **102** will be little or even the reflectivity of the reflective layer **102** will be improved. Moreover, if the thickness of the first layer **1031** and of the second layer **1032** is too thin, the first layer **1031** and the second layer **1032** cannot

play a better anti-oxidation effect and/or a better moisture isolation effect. If the thickness of the first layer **1031** and of the second layer **1032** is too thick, the reflectivity of the reflective layer **102** may be greatly reduced and production cost will be increased due to excessive waste of materials. Therefore, it is very important for improving the reflectivity of the reflective layer **102** and reducing the production cost to suitably set the thicknesses of the first layer **1031** and of the second layer **1032**.

(72) After a large number of experiments and practices by the inventors of the present application, it is finally determined that the thickness of each of the first layers may be set to a value in a range of 25 nm to 100 nm, and/or each of the second layers may be set to a value in a range of 25 nm to 100 nm. It is easy to understand that the thickness refers to a minimum distance (or called as a vertical distance) of a layer in the direction Z perpendicular to the plane where the light-emitting panel is located.

(73) In this way, when the thickness of the first layer and the thickness of the second layer are within the above-mentioned ranges, the first layer **1031** and the second layer **1032** can play a better anti-oxidation effect and/or a better moisture isolation effect, and moreover, reduction of the reflectivity of the reflective layer **102** will be little or even the reflectivity of the reflective layer **102** will be improved, and further materials consumed by the first layer and the second layer can be reduced so as to reduce production cost.

(74) For ease of understanding, an influence of the thickness of a layer in the protective layer **103** on the reflectivity of the reflective layer **102** will be described below with reference to some specific examples.

(75) FIG. 7 is a schematic diagram showing a relationship between a thickness of a layer in the protective layer and the reflectivity of the reflective layer. As shown in FIG. 7, a horizontal axis in FIG. 7 represents a thickness of a first layer or a second layer, and a vertical axis in FIG. 7 represents the reflectivity of the reflective layer **102**. In a case where the protective layer **103** includes one first layer **1031** (for example, the first layer **1031** has a material of MgO) and one second layer **1032** (for example, the second layer **1032** has a material of SiN.sub.x) and both the thickness of the first layer **1031** and the thickness of the second layer **1032** are (approximately) 70 nm, the reflectivity of the reflective layer **102** reaches the maximum, i.e. 80.89%. Compared with the reflectivity of the reflective layer **102** which is 82.52% (obtained by a simulation software) with no protective layer **103**, the reflectivity in this case is only reduced by $(82.52\% - 80.89\%) / 82.52\% = 2.0\%$ than that in the case where the protective layer **103** has not been applied.

(76) Table 1 schematically shows the reflectivity of the reflective layer **102** when the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of MgO) and two second layers **1032** (the second layer **1032** has a material of SiN.sub.x).

(77) TABLE-US-00001

TABLE 1		Thickness of SiNx		Thickness of MgO	
		25 nm	30 nm	35 nm	40 nm
25 nm	74.63%	78.63%	81.18%	82.51%	82.77%
30 nm	81.96%	82.77%	82.15%	80.41%	77.37%
35 nm	80.85%	82.32%	82.74%	82.15%	80.41%
40 nm	82.25%	82.74%	82.22%	80.61%	77.73%
45 nm	82.74%	82.30%	80.79%	78.05%	74.00%
50 nm	82.37%	80.95%	78.34%	74.47%	69.52%
					64.00%

(78) As shown in Table 1, the reflectivity of the reflective layer **102** reaches the maximum, i.e. 82.77% when the thickness of each first layer **1031** is 25 nm and the thickness of each second layer **1032** is 45 nm. Compared with a case where the reflectivity of the reflective layer **102** is 82.52% (obtained by a simulation software) when the protective layer **103** has not been applied, the reflectivity in this case is improved by $(82.77\% - 82.52\%) / 82.52\% = 0.3\%$ than that in the case where the protective layer **103** has not been applied. In addition, for the CIE 1931 standard chromaticity in this case, $L^* = 92.91$, $a^* = -2.6758$, and $b^* = 5.1351$, which meet expected requirements.

(79) It should be noted that data in FIG. 7 and Table 1 above are only schematic, and do not constitute a limitation to the embodiment of the present application.

(80) Still referring to FIG. 5 or FIG. 6, according to some embodiments of the present application,

optionally, in the direction Z perpendicular to the plane where the light-emitting panel **10** is located, the layer in the protective layer **103** that is closest to the substrate **100** is the second layer **1032**. A moisture absorption capability of a material of the first layer **1031** is greater than a moisture absorption capability of a material of the second layer **1032** and a moisture absorption capability of a material of the reflective layer **102**, and/or an anti-oxidation capability of the material of the second layer **1032** is greater than an anti-oxidation capability of the material of the first layer **1031** and an anti-oxidation capability of the material of the reflective layer **102**.

(81) That is, the first layer **1031** can be formed of a material having a better moisture absorption capability, and the second layer **1032** may be formed of a material having an anti-oxidation capability. Moreover, in the direction Z perpendicular to the plane where the light-emitting panel **10** is located, the outermost layer (that is farthest away from the substrate **100**) in the protective layer **103** is the first layer **1031**. In this way, since the first layer **1031** is disposed at the outermost side and the first layer **1031** is formed of a material having a better moisture absorption capability, the first layer **1031** can easily absorb moisture in the air, and thus can play a moisture isolation effect to a larger extent.

(82) According to some embodiments of the present application, optionally, the material of the first layer and/or the material of the second layer may be a transparent material or a translucent material. In other words, an extinction coefficient k (also known as absorbance) of the material of the first layer and/or the material of the second layer may be zero or approximately zero.

(83) In this way, absorption of light by the material of the first layer and/or the material of the second layer can be greatly reduced or even avoided, so that light emitted by the light-emitting elements can pass through the first layer and/or the second layer with almost no loss, thereby further improving the reflectivity of the reflective layer.

(84) In some specific embodiments, optionally, the material of the first layer **1031** may include magnesium oxide or oxynitride, and/or the material of the second layer **1032** may include silicon nitride, aluminum oxide, silica gel, acrylic material, epoxy or oxynitride. That is, the first layer **1031** may be formed of a material having a better moisture absorption capability, and the second layer **1032** may be formed of a material having a better anti-oxidation capability. It should be noted that, in addition to the materials listed above, the first layer **1031** and the second layer **1032** may be formed of other materials having similar material properties, which is not limited in the embodiment of the present application.

(85) Taking an oxynitride (such as silicon oxynitride SiN.sub.xO.sub.y) as an example, the oxynitride not only has a better moisture absorption capability, but also has a better anti-oxidation capability. Moreover, by adjusting a ratio of nitrogen N to oxygen O in the oxynitride, the oxynitride will have various refractive indexes, such as varying in a range of 1.4 to 2.0. Therefore, the oxynitride can be used for form the protective layer **103**. When forming the protective layer **103**, it is possible to form the first layer **1031** and the second layer **1032** with various refractive indexes by adjusting a ratio of nitrogen to oxygen in the oxynitride.

(86) Specifically, in some specific embodiments, optionally, both the material of the first layer **1031** and the material of the second layer **1032** are the oxynitride. Exemplarily, the oxynitride includes silicon oxynitride SiN.sub.xO.sub.y . A ratio of nitrogen to oxygen of the material of the first layer **1031** is smaller than a ratio of nitrogen to oxygen of the material of the second layer **1032**. It should be noted that it is general that the higher the ratio of nitrogen to oxygen in the oxynitride (i.e., a percentage of nitrogen), the higher the refractive index is. Therefore, for the case where the ratio of nitrogen to oxygen of the material of the first layer **1031** is smaller than the ratio of nitrogen to oxygen of the material of the second layer **1032**, it can be understood as that the refractive index of the material of the first layer **1031** is smaller than the refractive index of the material of the second layer **1032**. For example, in some examples, the material of the first layer **1031** may include $\text{SiO.sub.0.6N.sub.0.4}$, and the material of the second layer **1032** may include $\text{SiO.sub.0.2N.sub.0.8}$.

(87) In this way, since both the first layer **1031** and the second layer **1032** in the protective layer **103** are formed of oxynitride (such as the silicon oxynitride SiN.sub.xO.sub.y), it is possible to provide the first layer **1031** and the second layer **1032** that have different refractive indexes when forming the protective layer **103** by merely adjusting a ratio of nitrogen to oxygen (for example, adjusting an intake ratio of nitrogen gas and oxygen gas). That is, only one process is needed to form the protective layer **103** including layers with different refractive indexes, which is beneficial to simplification of processes. In addition, since oxynitride for forming the first layer **1031** and oxynitride for forming the second layer **1032** both have a better moisture absorption capability and a better anti-oxidation capability, the moisture absorption capability and anti-oxidation capability of the protective layer **103** can be further improved.

(88) For ease of understanding, following description are made with reference to some specific examples.

(89) Table 2 schematically shows the reflectivity of the reflective layer **102** when the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of $\text{SiO.sub.0.6N.sub.0.4}$) and two second layers **1032** (the second layer **1032** has a material of $\text{SiO.sub.0.2N.sub.0.8}$).

(90) TABLE-US-00002 TABLE 2 Thickness of Thickness of $\text{SiO.sub.0.2N.sub.0.8}$
 $\text{SiO.sub.0.6N.sub.0.4}$ 25 nm 30 nm 35 nm 40 nm 45 nm 50 nm 25 nm 71.92% 76.08% 79.19%
81.26% 82.4% 82.71% 30 nm 75.92% 79.04% 81.15% 82.34% 82.69% 82.24% 35 nm 78.92%
81.05% 82.28% 82.68% 82.28% 81.02% 40 nm 80.98% 82.23% 82.67% 82.32% 81.12% 79%
45 nm 82.2% 82.67% 82.35% 81.22% 79.18% 76.2% 50 nm 82.67% 82.39% 81.3% 79.33%
76.44% 72.76%

(91) As shown in Table 2, the reflectivity of the reflective layer **102** reaches the maximum, i.e. 82.71% when each first layer **1031** has a thickness of 25 nm and each second layer **1032** has a thickness of 50 nm. Compared with a case where the reflectivity of the reflective layer **102** is 82.52% (obtained by a simulation software) when the protective layer **103** has not been applied, the reflectivity in this case is improved by $(82.71\% - 82.52\%) / 82.52\% = 0.23\%$ than that in the case where the protective layer **103** has not been applied.

(92) FIG. 8 is a schematic diagram of hues of a CIE 1931 standard chromaticity system according to an embodiment of the application. As shown in FIG. 8, a horizontal axis of FIG. 8 represents an a^* color channel in the CIE 1931 standard chromaticity system, and a vertical axis of FIG. 8 represents a b^* color channel in the CIE 1931 standard chromaticity system. As shown in FIG. 8, the b^* varies in a range from 0 to 9 and the a^* varies in a range from -2 to -3 when the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of $\text{SiO.sub.0.6N.sub.0.4}$) and two second layers **1032** (the second layer **1032** has a material of $\text{SiO.sub.0.2N.sub.0.8}$), which meets expected requirements.

(93) FIG. 9 is a schematic diagram of a color gamut of the CIE 1931 standard chromaticity system according to an embodiment of the present application. As shown in FIG. 9, a horizontal axis of FIG. 9 represents coordinates of a color x in the CIE 1931 standard chromaticity system, and a vertical axis of FIG. 9 represents coordinates of a color y in the CIE 1931 standard chromaticity system. As shown in FIG. 9, when the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of $\text{SiO.sub.0.6N.sub.0.4}$) and two second layers **1032** (the second layer **1032** has a material of $\text{SiO.sub.0.2N.sub.0.8}$), there is a small fluctuation in the color gamut, that is, a coordinate of a white color at center merely fluctuates in a small range, which meets expected requirements.

(94) FIG. 10 is a schematic diagram of a relationship between wavelengths of light, incident angles and the reflectivity of the reflective layer according to an embodiment of the present application. An X-axis in FIG. 10 represents wavelengths in nm; a Y-axis in FIG. 10 represents incident angles; and a Z-axis in FIG. 10 represents the reflectivity. As shown in FIG. 10, in a case where the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of

SiO.sub.0.6N.sub.0.4) and two second layers **1032** (the second layer **1032** has a material of SiO.sub.0.2N.sub.0.8), if the wavelength is within a range of 400 nm to 700 nm, the reflectivity corresponding to each of different incident angles reaches more than 70%, which is a higher reflectivity.

(95) The inventors of the present application have further found that process requirements for the reflective layer **102** are that it has a uniform thickness and has no defects such as air bubbles and perforations, but the reflective layer **102** practically has a surface roughness in an order of μm . In this way, since the reflective layer **102** has a larger surface roughness, it is not conducive to realization of surface coating.

(96) In view of this, the inventors of the present application anticipate that before the protective layer **103** is formed, a planarization layer is formed on the reflective layer **102** to facilitate forming of the protective layer **103**. FIG. **11** is another schematic cross-sectional view of the light-emitting panel shown in FIG. **1** along the A-A' direction. Specifically, as shown in FIG. **11**, according to some embodiments of the present application, optionally, the light-emitting panel **10** may further include a planarization layer **901**, and in a direction Z perpendicular to the plane where the light-emitting panel **10** is located, the planarization layer **901** may be located between the protective layer **103** and the reflective layer **102**. Exemplarily, the planarization layer **901** may include, but is not limited to, OC optical cement.

(97) In this way, by providing the planarization layer **901** between the protective layer **103** and the reflective layer **102**, coating of the protective layer **103** can be facilitated, and the protective layer **103** can be prevented from peeling off easily.

(98) According to some embodiments of the present application, optionally, in the direction Z perpendicular to the plane where the light-emitting panel is located, the planarization layer **901** may have a thickness in a range of 5 μm to 20 μm .

(99) The reason why the thickness of the planarizing layer **901** in the embodiment of the present application is set to a value in the range of 5 μm to 20 μm is that the inventors have found that when the thickness of the planarizing layer **901** is less than 5 μm , a surface of the planarizing layer **901** that is facing away from the reflective layer **102** is still not flat enough, which is not conducive to coating of the protective layer **103**; and when the thickness of the planarization layer **901** is greater than 20 μm , the reflectivity of the reflective layer **102** may be reduced due to too thick thickness of the planarization layer **901** and production cost will be increased. Therefore, setting the thickness of the planarization layer **901** to be a value in the range of 5 μm to 20 μm not only facilitates coating of the protective layer **103** but also ensures that the reflective layer **102** has a higher reflectivity and maintains a reduced production cost.

(100) In some specific examples, the thickness of the planarization layer **901** is, for example, 10 μm . For ease of understanding, detailed descriptions are given below with reference to some specific examples.

(101) Table 3 schematically shows that the reflectivity of the reflective layer **102** when the thickness of the planarization layer **901** is 10 μm and the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of MgO) and two second layers **1032** (the first layer **1032** has a material of SiN.sub.x).

(102) TABLE-US-00003 TABLE 3 Thickness Thickness of SiNx of MgO 25 nm 30 nm 35 nm 40 nm 45 nm 50 nm 55 nm 60 nm 25 nm 70.35% 69.13% 69.52% 71.85% 75.05% 77.86% 79.81% 80.74% 30 nm 69.25% 69.54% 71.74% 74.88% 77.70% 79.70% 80.71% 80.80% 35 nm 69.56% 71.64% 74.71% 77.54% 79.58% 80.67% 80.83% 80.41% 40 nm 71.55% 74.56% 77.39% 79.46% 80.61% 80.84% 80.47% 79.74% 45 nm 74.41% 77.23% 79.33% 80.54% 80.84% 80.50% 79.81% 78.78% 50 nm 77.08% 79.20% 80.45% 80.81% 80.52% 79.86% 78.86% 77.55%

(103) As shown in Table 3, in a case where the planarization layer **901** with a thickness of 10 μm is provided and the thickness of each first layer **1031** is 45 nm and the thickness of each second layer **1032** is 45 nm, the reflectivity of the reflective layer **102** reaches the maximum, i.e. 80.84%.

Compared with a case where the reflectivity of the reflective layer **102** is 82.52% (obtained by a simulation software) when the protective layer **103** has not been applied, the reflectivity in this case is decreased only by $(82.52\%-80.84\%)/82.52\%=2.0\%$ than that when the protective layer **103** has not been applied. In addition, for the CIE 1931 standard chromaticity, $L^*=89.95$, $a^*=-0.2320$, $b^*=0.0282$ in this case, which meets expected requirements.

(104) Table 4 schematically shows the reflectivity of the reflective layer **102** when the thickness of the planarization layer **901** is 10 μm and the protective layer **103** includes two first layers **1031** (the first layer has a material of SiO_2 and 0.6N) and two second layers **1032** (the second layer **1032** has a material of SiO_2 and 0.2N).

(105) TABLE-US-00004 TABLE 4 Thickness of Thickness of SiO_2 and 0.2N and 0.8

SiO_2 and 0.6N	25 nm	30 nm	35 nm	40 nm	45 nm	50 nm	25 nm	71.67%	70.35%	69.88%
SiO_2 and 0.6N	30 nm	70.45%	69.95%	70.74%	72.76%	75.26%	77.5%	35 nm	70%	
SiO_2 and 0.6N	35 nm	70.75%	72.7%	75.17%	77.42%	79.1%	40 nm	70.75%	72.65%	75.09%
SiO_2 and 0.6N	40 nm	70.75%	72.65%	75.09%	77.33%	79.03%	45 nm	72.6%	75.01%	77.25%
SiO_2 and 0.6N	45 nm	72.6%	75.01%	77.25%	78.96%	80.04%	50 nm	74.93%	77.16%	78.89%
SiO_2 and 0.6N	50 nm	74.93%	77.16%	78.89%	79.98%	80.41%		80.27%		

(106) As shown in Table 4, in a case where the planarization layer **901** with a thickness of 10 μm is provided and the thickness of each first layer **1031** is 45 nm and the thickness of each second layer **1032** is 50 nm, the reflectivity of the reflective layer **102** reaches the maximum, i.e. 80.43%.

Compared with a case where the reflectivity of the reflective layer **102** is 82.52% (obtained by a simulation software) when the protective layer **103** has not been applied, the reflectivity in this case is decreased only by $(82.52\%-80.43\%)/82.52\%=2.53\%$ than that when the protective layer **103** has not been applied.

(107) FIG. 12 is another schematic diagram of hues of the CIE 1931 standard chromaticity system according to an embodiment of the application. A horizontal axis of FIG. 12 represents an a^* color channel in the CIE 1931 standard chromaticity system, and a vertical axis of FIG. 12 represents a b^* color channel in the CIE 1931 standard chromaticity system. As shown in FIG. 8 and FIG. 12, after the planarization layer **901** is provided, a range of variation of b^* and a range of variation of a^* in FIG. 12 are obviously reduced compared with that in FIG. 8, wherein the b^* varies merely in a range from 0.15 to 0.3, the a^* varies merely in a range from -0.15 to -0.3.

(108) FIG. 13 is another schematic diagram of a color gamut of the CIE 1931 standard chromaticity system according to an embodiment of the application. A horizontal axis of FIG. 13 represents coordinates of a color x in the CIE 1931 standard chromaticity system, and a vertical axis of FIG. 13 represents coordinates of a color y in the CIE 1931 standard chromaticity system. As shown in FIGS. 9 and 13, after the planarization layer **901** is provided, fluctuation of the color gamut in FIG. 13 becomes smaller compared with that in FIG. 9, wherein the coordinate of the white color at center fluctuate in a smaller range, and the fluctuation of the color gamut become more stable.

(109) FIG. 14 is a schematic diagram showing another relationship between wavelengths of light, incident angles and the reflectivity of the reflective layer according to an embodiment of the present application. An X-axis in FIG. 14 represents wavelengths in nm; a Y-axis in FIG. 14 represents incident angles; and a Z-axis in FIG. 14 represents the reflectivity. As shown in FIG. 14, after the planarization layer **901** is provided and in a case where the protective layer **103** includes two first layers **1031** (the first layer **1031** has a material of SiO_2 and 0.6N) and two second layers **1032** (the second layer **1032** has a material of SiO_2 and 0.2N), if the wavelength is within a range of 400 nm to 700 nm, the reflectivity corresponding to each of different incident angles reaches more than 70%, which is a higher reflectivity.

(110) It should be noted that data in the above-mentioned FIGS. 8 to 14 and Tables 2 to 4 are only schematic, and do not constitute limitations to the embodiments of the present application.

(111) According to some embodiments of the present application, optionally, a material of the planarization layer may be a transparent material or a translucent material. In other words, an extinction coefficient k (also known as absorbance) of the material of the planarization layer may

be zero or approximately zero.

(112) In this way, absorption of light by the material of the planarization layer can be greatly reduced or even avoided, so that light emitted by the light-emitting elements can pass through the planarization layer with almost no loss, thereby further improving the reflectivity of the reflective layer.

(113) FIG. 15 is a schematic cross-sectional view of a light-emitting panel according to an embodiment of the present application. As shown in FIG. 15, according to some embodiments of the present application, optionally, the substrate **100** may be provided with a plurality of light-condensing grooves **1300** in order to improve an efficiency of light outputting of the light-emitting panel **10**. In a direction Z perpendicular to a plane where the light emitting panel **10** is located, the light-condensing grooves **1300** are at least overlapped with the openings **k1**. The reflective layer **102** and protective layer **103** are stacked and disposed on surfaces of the light-condensing grooves **1300**, and the bonding points **201** may be disposed within the light-condensing grooves **1300**. It should be noted that a shape and size of the light-condensing groove **1300** may be flexibly adjusted according to an actual situation, which is not limited in the embodiment of the present application. Exemplarily, the light-condensing groove **1300** may be a curved groove, for example.

(114) In this way, by providing the light-condensing grooves **1300**, the light emitted by the light-emitting elements **101** can be condensed and then reflected, which increases a divergence angle of the light emitted by the light-emitting elements **101** and thereby improves a luminous effect of the light-emitting panel.

(115) FIG. 16 is another schematic cross-sectional view of the light-emitting panel shown in FIG. 1 along the A-A' direction. As shown in FIG. 16, according to some embodiments of the present application, optionally, the light-emitting panel **10** may further include a sealing layer **1400** in order to avoid invalidation of the protective layer **103** due to damages, and in a direction Z perpendicular to the plane where the light-emitting panel is located, the sealing layer **1400** is disposed at a side of the protective layer **103** that is away from the substrate **100**. It is easy to understand that the sealing layer **1400** is provided with openings **k2**, and in the direction Z perpendicular to the plane where the light-emitting panel is located, the openings **k2** of the sealing layer **1400** are at least overlapped with the openings **k1** of the protective layer **103** and the reflective layer **102** so as to expose the bonding points **201**. Exemplarily, a material of the sealing layer **1400** may include, but is not limited to, epoxy resin, silica gel or any other material with a higher light transmittance.

(116) In this way, by providing the sealing layer **1400** at the side of the protective layer **103** that is away from the substrate **100**, the protective layer **103** can be well protected and prevented from being scratched, thereby preventing invalidation of the protective layer **103** due to damages.

(117) On the basis of the light-emitting panel according to the above-mentioned embodiments, the present application also provides a method for fabricating a light-emitting panel, and the method for fabricating a light-emitting panel can be used to fabricate the light-emitting panel **10** according to the above-mentioned embodiments, for example.

(118) FIG. 17 is a schematic flowchart of a method for fabricating a light-emitting panel according to an embodiment of the present application. As shown in FIG. 17, the method for fabricating a light-emitting panel according to an embodiment of the present application includes following steps **S101** to **S104**.

(119) At **S101**, a substrate is provided, wherein the substrate is provided with bonding points.

(120) FIG. 18 is a process schematic diagram of a method for fabricating a light-emitting panel according to an embodiment of the present application. Referring to FIG. 18, at **S101**, a substrate **100** is provided, wherein the substrate **100** is provided with bonding points **201**. The substrate **100** may include, but is not limited to, a rigid substrate, and the rigid substrate may include, but is not limited to, a glass substrate, a printed circuit board (Printed Circuit Board, PCB) substrate, or any other rigid substrate.

(121) At **S102**, a reflective layer is formed at a side of the substrate where the bonding points are

located.

(122) Referring to FIG. 18, at S102, a reflective layer 102 may be formed by spraying on the side of the substrate 100 where the bonding points 201 are disposed. The reflective layer 102 may include, but is not limited to, white reflective ink (referred as white ink for short), and the reflective layer 102 may be formed of any other material having a higher reflectivity in addition to the white reflective ink, which is not limited in the embodiment of the present application.

(123) At S103, a protective layer is formed at a side of the reflective layer that is away from the substrate, and openings are formed on both the protective layer and the reflective layer to expose the bonding points.

(124) Referring to FIG. 18, at S103, a protective layer 103 may be formed at a side of the reflective layer 102 that is away from the substrate 100, and openings k1 may be formed on the protective layer 103 and the reflective layer 102 through a patterning process to expose the bonding points 201. It should be noted that the openings on the reflective layer 102 may be provided by a patterning process before forming of the protective layer, as long as it is ensured that the openings on the protective layer 103 are overlapped with the openings on the reflective layer 102 in the direction perpendicular to the plane where the light-emitting panel is located.

(125) At S104, light-emitting elements are electrically connected to the bonding points.

(126) Referring to FIG. 18, at S104, light-emitting elements 101 may be electrically connected by welding or any other bonding method (e.g., conductive adhesive bonding) to the bonding points 201, for example.

(127) In the method for fabricating a light-emitting panel according to an embodiment of the present application, by providing the protective layer 103 at the side of the reflective layer 102 that is away from the substrate 100, the protective layer 103 can play an anti-oxidation effect, and thus oxidation of the reflective layer 102 during a bonding process of the light-emitting elements 101 or a light-emitting process of the light-emitting elements 101 can be reduced or even avoided, thereby reducing or even avoiding yellowing of the reflective layer 102, and thus a light-outputting effect of the light-emitting panel 10 can be improved, and/or the protective layer 103 can play a moisture isolation effect to prevent intrusion of moisture as much as possible, thereby reducing or even avoiding corrosion of wirings or electronic devices in the light-emitting elements 101 and in the substrate 100.

(128) FIG. 19 is another process schematic diagram of a method for fabricating a light-emitting panel according to an embodiment of the present application. As shown in FIG. 19, in some embodiments, before the light-emitting elements are electrically connected to the bonding points at S104, the method for fabricating the light-emitting panel may further include the following steps: forming a sealing layer 1400 at a side of the protective layer 103 that is away from the substrate 100, and forming openings k2 on the sealing layer 1400, wherein the openings k2 on the sealing layer 1400 are at least overlapped with the openings k1 on the protective layer 103 and the reflective layer 102 to expose the bonding points 201. Exemplarily, the sealing layer 1400 has a material which may include, but is not limited to, epoxy resin, silica gel or any other material having a higher light transmittance.

(129) In this way, by providing the sealing layer 1400 at the side of the protective layer 103 that is away from the substrate 100, the protective layer 103 can be well protected and prevented from being scratched, thereby preventing invalidation of the protective layer 103 due to damages.

(130) In some embodiments, after the reflective layer is formed at the side of the substrate where the bonding points are disposed at S102 but before the protective layer is formed at the side of the reflective layer that is away from the substrate at S103, the method for fabricating the light-emitting panel may further include the following step: forming a planarization layer 901 at a side of the reflective layer 102 that is away from the substrate 100, as shown in FIG. 11. The planarization layer 901 is provided with openings. In a direction Z perpendicular to a plane where the light-emitting panel is located, the openings on the planarization layer 901 are at least overlapped with

the openings **k1** on the protective layer **103** and the reflective layer **102** to expose the bonding points **201**. Exemplarily, the planarization layer **901** may include, but is not limited to, OC optical adhesive.

(131) In this way, by providing the planarization layer **901** between the protective layer **103** and the reflective layer **102**, it can facilitate coating of the protective layer **103** and prevent the protective layer **103** from falling off easily.

(132) In some embodiments, before **S101**, the method for fabricating the light-emitting panel may further include the following steps: providing a plurality of light-condensing grooves **1300** on the substrate **100**, as shown in FIG. **15**, and forming the bonding points **201** within the light-condensing grooves **1300**. It should be noted that a shape and size of the light-condensing groove **1300** may be flexibly adjusted according to an actual situation, which is not limited in the embodiment of the present application.

(133) In this way, by providing the light-condensing grooves **1300**, the light emitted by the light-emitting elements **101** can be condensed and then reflected, which increases a divergence angle of the light emitted by the light-emitting elements **101** and thereby improves a luminous effect of the light-emitting panel.

(134) In some embodiments, the protective layer **103** may include a first layer **1031** and a second layer **1032** that have different refractive indices. The **S103** may specifically include: sequentially forming stacked second layer **1032** and first layer **1031** at a side of the reflective layer **102** that is away from the substrate **100**, and providing openings **k1** on the first layer **1031**, the second layer **1032** and the reflective layer **102** to expose the bonding points **201**.

(135) It should be noted that the method for fabricating the light-emitting panel in the above method embodiments attains technical effects corresponding to that of the light-emitting panel **10** in the above product embodiments, which are not repeated here for sake of brevity.

(136) On the basis of the light-emitting panel according to the above embodiments, the present application also provides a display device accordingly. As shown in FIG. **20**, the display device **1000** may include a device body **20'** and the light-emitting panel **10** in the above-mentioned embodiments, wherein the light-emitting panel **10** is overlaid on the device body **20'**. In the device body **20'**, there may be provided various types of devices, such as sensors, processors, etc., which are not limited herein. The display device **1000** may specifically be a device having a display function, such as a mobile phone, a computer, a tablet computer, a digital camera, a television, and an electronic paper, which is not limited herein.

(137) As shown in FIG. **21**, in some embodiments, the light-emitting panel **10** may be a backlight panel, and the display device **1000** may further include a display panel **30** at a side of a light-emitting surface of the backlight panel (as shown by the surface **a** in FIG. **21**).

(138) It should be clear that the embodiments in the specification are described in a progressive manner, and same or similar parts of respective embodiments can be referred to each other, and each embodiment focuses on differences from other embodiments. For the embodiments of the display panel and the embodiments of the display device, references may be made to those descriptions of the embodiments of the pixel driving circuit and the embodiments of the array substrate. The present application is not limited to the specific structures described above and shown in the drawings. Various changes, modifications and additions can be made by a person skilled in the art after comprehending spirits of the present application. Also, for sake of brevity, detailed descriptions of known technologies are omitted here.

(139) It should be understood for a person skilled in the art that the above-mentioned embodiments are all illustrative and not restrictive. Different technical features appearing in different embodiments can be combined to achieve beneficial effects. A person skilled in the art will be able to understand and implement other variant embodiments of the described embodiments after studying the drawings, the description and the claims. In the claims, the term “comprising” does not exclude other structures; a quantity referring to “one” does not exclude more than one; the

terms “first”, “second” are used to designate names and not to indicate any particular order. Any reference signs in the claims shall not be construed as limiting the protection scope. The mere presence of certain technical features in different dependent claims does not imply that these features cannot be combined to achieve beneficial effects.

Claims

1. A light-emitting panel, comprising: a substrate, and a plurality of light-emitting elements, a reflective layer and a protective layer that are disposed at a side of the substrate, wherein the reflective layer is located between the substrate and the protective layer; and wherein both the protective layer and the reflective layer are provided with openings, the substrate comprises bonding points within the openings, and the light-emitting elements are electrically connected to the bonding points.
2. The light-emitting panel according to claim 1, wherein the protective layer comprises at least one first layer with a first refractive index and at least one second layer with a second refractive index, and the first refractive index is different from the second refractive index.
3. The light-emitting panel according to claim 2, wherein the protective layer comprises one first layer and one second layer; and wherein in a direction perpendicular to a plane where the light-emitting panel is located, the first layer is disposed at a side of the second layer that is away from the substrate, and the second refractive index is greater than the first refractive index.
4. The light-emitting panel according to claim 2, wherein the protective layer comprises at least two first layers and at least two second layers; and wherein in a direction perpendicular to a plane where the light-emitting panel is located, the first layers and the second layers are alternately arranged.
5. The light-emitting panel according to claim 4, wherein in the direction perpendicular to the plane where the light-emitting panel is located, a layer in the protective layer that is closest to the substrate is the second layer and the second refractive index is greater than the first refractive index.
6. The light-emitting panel according to claim 2, wherein each of the first refractive index and the second refractive index has a value in a range of 1.4 to 2.0.
7. The light-emitting panel according to claim 2, wherein in a direction perpendicular to a plane where the light-emitting panel is located, a layer in the protective layer that is closest to the substrate is the second layer; and wherein a moisture absorption capability of a material of the first layer is greater than a moisture absorption capability of a material of the second layer and a moisture absorption capability of a material of the reflective layer, or an anti-oxidation capability of the material of the second layer is greater than an anti-oxidation capability of the material of the first layer and an anti-oxidation capability of the material of the reflective layer.
8. The light-emitting panel according to claim 2, wherein each first layer has a thickness in a range of 25 nm to 100 nm, or each second layer has a thickness in a range of 25 nm to 100 nm.
9. The light-emitting panel according to claim 2, wherein a material of the first layer is a transparent material or a translucent material, or a material of the second layer is a transparent material or a translucent material.
10. The light-emitting panel according to claim 2, wherein a material of the first layer comprises magnesium oxide or oxynitride, or a material of the second layer comprises silicon nitride, aluminum oxide, silicone, acrylic material, epoxy or oxynitride.
11. The light-emitting panel according to claim 10, wherein both the material of the first layer and the material of the second layer are the oxynitride, wherein the oxynitride comprises silicon oxynitride, and wherein a ratio of nitrogen to oxygen of the material of the first layer is smaller than a ratio of nitrogen to oxygen of the material of the second layer.
12. The light-emitting panel according to claim 1, wherein the light-emitting panel further

- comprises a planarization layer, and in a direction perpendicular to a plane where the light-emitting panel is located, the planarization layer is located between the protective layer and the reflective layer.
13. The light-emitting panel according to claim 12, wherein in the direction perpendicular to the plane where the light-emitting panel is located, the planarization layer has a thickness in a range of 5 μm to 20 μm .
14. The light-emitting panel according to claim 12, wherein a material of the planarization layer comprises a transparent material or a translucent material.
15. The light-emitting panel according to claim 1, wherein a plurality of light-condensing grooves are provided on the substrate, and in a direction perpendicular to a plane where the light-emitting panel is located, the light-condensing grooves are at least overlapped with the openings, and wherein the reflective layer and the protective layer are stacked and disposed on surfaces of the light-condensing grooves, and the bonding points are located within the light-condensing grooves.
16. The light-emitting panel according to claim 1, wherein the light-emitting panel further comprises a sealing layer, and in a direction perpendicular to a plane where the light-emitting panel is located, the sealing layer is disposed at a side of the protective layer that is away from the substrate; and wherein the sealing layer is provided with openings, and the openings of the sealing layer are at least overlapped with the openings of both the protective layer and the reflective layer.
17. The light-emitting panel according to claim 1, wherein the protective layer covers side faces of the reflective layer that are close to the bonding points.
18. A method for fabricating a light-emitting panel that comprises the light-emitting panel according to claim 1, the method comprising: providing a substrate on which bonding points are provided; forming a reflective layer at a side of the substrate where the bonding points are located; forming a protective layer at a side of the reflective layer that is away from the substrate, and forming openings on both the protective layer and the reflective layer to expose the bonding points; and electrically connecting light-emitting elements to the bonding points.
19. The method according to claim 18, wherein before electrically connecting the light-emitting elements to the bonding points, the method further comprises: forming a sealing layer at a side of the protective layer that is away from the substrate, and forming openings on the sealing layer, wherein the openings of the sealing layer are at least overlapped with the openings of both the protective layer and the reflective layer to expose the bonding points.
20. A display device, comprising the light-emitting panel according to claim 1.
-