

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12411401
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Jang; Naewon et al.

Screen for projector and manufacturing method thereof

Abstract

A projector screen includes: a light absorbing layer configured to absorb light; a plurality of reflectors provided on a front surface of the light absorbing layer and spaced apart from each other at regular intervals, wherein the plurality of reflectors are inclined with respect to the light absorbing layer and are configured to reflect light; and a transparent layer disposed above the plurality of reflectors and configured to transmit light therethrough, wherein the transparent layer may include a front surface that is flat and parallel to the light absorbing layer, and a rear surface having a plurality of grooves having a shape corresponding to the plurality of reflectors, wherein the plurality of reflectors are provided in the plurality of grooves of the transparent layer, and the rear surface of the transparent layer contacts the front surface of the light absorbing layer.

Inventors:	Jang; Naewon (Suwon-si, KR), Lee; Youngchol (Suwon-si, KR)
Applicant:	SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)
Family ID:	82357210
Assignee:	SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)
Appl. No.:	18/214123
Filed:	June 26, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230333458 A1	Oct. 19, 2023

Foreign Application Priority Data

KR	10-2021-0001093	Jan. 05, 2021
----	-----------------	---------------

Related U.S. Application Data

Publication Classification

Int. Cl.: **G03B21/60** (20140101); **G02B5/00** (20060101); **G03B21/56** (20060101); **G03B21/602** (20140101); **G03B21/604** (20140101); **G03B21/625** (20140101)

U.S. Cl.:

CPC **G03B21/60** (20130101); **G02B5/003** (20130101); **G03B21/56** (20130101); **G03B21/602** (20130101); **G03B21/604** (20130101); **G03B21/625** (20130101);

Field of Classification Search

CPC: G03B (21/60); G03B (21/602); G03B (21/56); G03B (21/625); G03B (21/604); G02B (5/003)

USPC: 359/459

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
7035006	12/2005	Umeya	359/10	G02B 5/0284
8711475	12/2013	Jeon	359/449	G03B 21/60
9354500	12/2015	Kim	N/A	G02B 30/27
2014/0036359	12/2013	Jeon	427/163.3	G03B 21/60
2023/0333458	12/2022	Jang	N/A	G02B 5/003

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
9-34015	12/1996	JP	N/A
2005-114953	12/2004	JP	N/A
2010-204572	12/2009	JP	N/A
2014115581	12/2013	JP	N/A
2015227971	12/2014	JP	N/A
2016075846	12/2015	JP	N/A
6536003	12/2018	JP	N/A
1998-033106	12/1997	KR	N/A
10-0294218	12/2000	KR	N/A
10-2004-0007333	12/2003	KR	N/A
10-2012-0069180	12/2011	KR	N/A
20120069180	12/2011	KR	G03B 21/56
10-2013-0022987	12/2012	KR	N/A
20130022987	12/2012	KR	G02B 5/00
10-2014-0119986	12/2013	KR	N/A

OTHER PUBLICATIONS

Written Opinion (PCT/ISA/237) issued Apr. 6, 2022 by the International Searching Authority in International Application No. PCT/KR2021/019637. cited by applicant

International Search Report (PCT/ISA/210) issued Apr. 6, 2022 by the International Searching Authority in International Application No. PCT/KR2021/019637. cited by applicant

Primary Examiner: Bloss; Stephanie E

Assistant Examiner: Butler; Kevin C

Attorney, Agent or Firm: Sughrue Mion, PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is by-pass continuation application of International Application No. PCT/KR2021/019637, filed on Dec. 22, 2021, which based on and claims priority to Korean Patent Application No. 10-2021-0001093, filed on Jan. 5, 2021, in the Korean Intellectual Property Office, the disclosures of which are incorporated by reference herein in their entireties.

BACKGROUND

1. Field

(1) The disclosure relates to a projector screen and a method of manufacturing the projector screen.

2. Description of Related Art

(2) When a projector projects image light onto a screen, the user may see an image through the image light reflected on the screen.

(3) Because the incident angle and reflection angle of the image light are symmetrical, in the case of a general projector that projects image light onto the screen at a long distance, the image light projected from the projector may be reflected on the screen and transmitted to the user.

(4) However, in the case of a short throw projector that projects image light onto the screen at a short distance, the incident angle of the image light incident on the screen is larger than that of the general projector.

(5) When the incident angle of the image light is large, the reflection angle is also large, so most of the image light is reflected toward the ceiling instead of toward the user. Thus, the user sees a dark image.

(6) In attempt to solve this problem, a screen for the short throw projector has been developed and used.

(7) FIG. 1 is a cross-sectional view illustrating a projector screen according to the related art.

(8) Referring to FIG. 1, the projector screen **100** according to the related art includes an absorption pattern layer **101**, a plurality of reflective surfaces **103**, and a transparent layer **105**.

(9) The absorption pattern layer **101** is formed to absorb external light G coming from the ceiling and not reflect it toward the user. On the front surface of the absorption pattern layer **101**, a plurality of protrusions **102** having an isosceles triangular cross-section are continuously formed. Therefore, the external light G is incident to the absorption pattern layer **101** through the upper inclined surfaces of the plurality of protrusions **102** and is not reflected to the outside.

(10) The plurality of reflective surfaces **103** are formed to reflect image light L emitted from the projector disposed below the projector screen **100** toward the user. The plurality of reflective surfaces **103** are formed on lower inclined surfaces of the plurality of protrusions **102** of the

absorption pattern layer **101**.

(11) The plurality of reflective surfaces **103** may be formed by depositing a reflective material on the lower inclined surfaces of the plurality of protrusions **102** by sputtering or by coating the lower inclined surfaces thereof with white ink.

(12) The transparent layer **105** is disposed in front of the absorption pattern layer **101** and the plurality of reflective surfaces **103** to form the front surface of the screen **100**, and transmits external light G and image light L.

(13) Accordingly, the projector screen **100** according to the related art having the structure shown in FIG. **1** may reflect image light L incident from the lower side toward the user and absorb external light G incident from the ceiling.

(14) However, because the projector screen **100** according to the related art as described above is formed by sputtering a reflective material or coating white ink on the lower inclined surfaces of the plurality of protrusions **102** of the absorption pattern layer **101**, the manufacturing cost is high.

(15) In addition, depending on the precision of the plurality of reflective surfaces **103** formed on the lower inclined surface of the plurality of protrusions **102** of the absorption pattern layer **101**, the black level by external light G may be increased. When the black level is high, the bright-room contrast ratio is reduced, resulting in deterioration of image quality.

SUMMARY

(16) Provided is a projector screen that may improve a contrast ratio in a bright room with a low manufacturing cost.

(17) In addition, provided is a method of manufacturing a projector screen that may improve a contrast ratio in a bright room with a low manufacturing cost.

(18) According to an aspect of the disclosure, a projector screen includes: a light absorbing layer configured to absorb light; a plurality of reflectors provided on a front surface of the light absorbing layer and spaced apart from each other at regular intervals, wherein the plurality of reflectors are inclined with respect to the light absorbing layer and are configured to reflect light; and a transparent layer disposed above the plurality of reflectors and configured to transmit light therethrough, wherein the transparent layer may include a front surface that is flat and parallel to the light absorbing layer, and a rear surface having a plurality of grooves having a shape corresponding to the plurality of reflectors, wherein the plurality of reflectors are provided in the plurality of grooves of the transparent layer, and the rear surface of the transparent layer contacts the front surface of the light absorbing layer.

(19) A cross-section of each reflector of the plurality of reflectors may have a shape of a right triangle, and each reflector of the plurality of reflectors may include a rear surface that contacts the light absorbing layer and may be a base of the shape of the right triangle.

(20) A cross-section of each reflector of the plurality of reflectors may have a shape of a trapezoid, and each reflector of the plurality of reflectors may include a rear surface that contacts the light absorbing layer and may be a side of the shape of the trapezoid.

(21) Each reflector of the plurality of reflectors may include a reflective surface inclined with respect to the light absorbing layer and configured to reflect light, and a ratio of a base of the reflective surface to a height of the reflective surface may be at least 0.5.

(22) The plurality of reflectors may include white beads.

(23) The transparent layer may include a transparent urethane resin.

(24) The projector screen may further include a base film that may be disposed on the front surface of the transparent layer and may be transparent.

(25) The projector screen may further include a low reflection layer disposed on a front surface of the base film.

(26) The projector screen may further include a color absorption layer disposed on a front surface of the low reflection layer.

(27) According to an aspect of the disclosure, a method of manufacturing a projector screen,

includes: forming a transparent layer on a first surface of a base film; forming a plurality of grooves on an upper surface of the transparent layer, wherein each groove of the plurality of grooves has a right triangle cross-section and the plurality of grooves are spaced apart from each other at regular intervals; filling the plurality of grooves with at least one of white beads or white resin; and disposing a light absorbing layer on the upper surface of the transparent layer in which the plurality of grooves are formed.

(28) Each groove of the plurality of grooves may have a ratio of an opening width to a height may be at least 0.5.

(29) The forming the plurality of grooves on the upper surface of the transparent layer may include forming the plurality of grooves on the upper surface of the transparent layer by performing an imprinting process.

(30) The method may further include: forming a low reflection layer on a second surface of the base film that may be different than the first surface; and forming a color absorption layer on a surface of the low reflection layer that does not contact with the base film.

(31) According to an aspect of the disclosure, a method of manufacturing a projector screen, includes: forming a transparent layer on a surface of a base film; forming a plurality of grooves on an upper surface of the transparent layer, wherein each groove of the plurality of grooves has a rectangular cross-section and the plurality of grooves are spaced apart from each other at regular intervals; filling the plurality of grooves with white beads; molding the transparent layer by using a roller such that the plurality of grooves filled with the white beads are inclined with respect to the base film; and disposing a light absorbing layer on the upper surface of the transparent layer molded by the roller.

(32) Each groove of the plurality of grooves having a rectangular cross-section inclined in the molding the transparent layer may be formed so that a ratio of a base of an inclined side to a height of the inclined side is at least 0.5.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The above and other aspects, features, and advantages of certain embodiments of the present disclosure will be more apparent from the following description taken in conjunction with the accompanying drawings, in which:

(2) FIG. 1 is a cross-sectional view illustrating a projector screen according to the related art;

(3) FIG. 2 is a view illustrating a display apparatus including a projector screen according to an embodiment of the disclosure;

(4) FIG. 3 is a cross-sectional view illustrating a projector screen according to an embodiment of the disclosure;

(5) FIG. 4 is a partially enlarged cross-sectional view illustrating a reflector of a projector screen according to an embodiment of the disclosure;

(6) FIG. 5 is a view illustrating paths of image light and external light incident on a projector screen according to an embodiment of the disclosure;

(7) FIGS. 6A to 6E are views for explaining a method of manufacturing a projector screen according to an embodiment of the disclosure;

(8) FIG. 7 is a cross-sectional view illustrating a projector screen according to an embodiment of the disclosure;

(9) FIG. 8 is a graph illustrating absorption spectra according to wavelength bands of light;

(10) FIG. 9 is a graph comparing light intensity of a projector screen including a color absorbing layer capable of absorbing yellow light and light intensity of a projector screen without a color absorbing layer;

- (11) FIG. 10 is a graph illustrating a spectrum of image light projected from a projector;
- (12) FIG. 11 is a cross-sectional view illustrating a projector screen according to an embodiment of the disclosure;
- (13) FIG. 12 is a partially enlarged cross-sectional view illustrating a reflector of a projector screen according to an embodiment of the disclosure;
- (14) FIG. 13 is a view illustrating paths of image light and external light incident on a projector screen according to an embodiment of the disclosure;
- (15) FIGS. 14A to 14F are views for explaining a method of manufacturing a projector screen according to an embodiment of the disclosure; and
- (16) FIG. 15 is a cross-sectional view illustrating a projector screen according to an embodiment of the disclosure.

DETAILED DESCRIPTION

- (17) Various embodiments described below are shown by way of example to assist understanding of the disclosure, and it should be understood that the disclosure may be variously modified and implemented differently from the embodiments described herein. However, in the following description of the disclosure, when it is determined that a detailed description of a related known function or components may unnecessarily obscure the gist of the disclosure, the detailed description and specific illustration thereof will be omitted. Further, in the accompanying drawings, the dimensions of some components may be arbitrarily exaggerated and not drawn to scale in order to aid understanding of the disclosure.
- (18) The terms ‘first’, ‘second’, etc. may be used to describe diverse components, but the components are not limited by the terms. The terms may only be used to distinguish one component from the others. For example, without departing from the scope of the disclosure, a first component may be referred to as a second component, and similarly, a second component may also be referred to as a first component.
- (19) The terms used in embodiments of the disclosure may be construed as commonly known to those skilled in the art unless otherwise defined.
- (20) Further, the terms ‘leading end’, ‘rear end’, ‘upper side’, ‘lower side’, ‘top end’, ‘bottom end’, etc. used in the disclosure are defined with reference to the drawings. However, the shape and position of each component are not limited by the terms.
- (21) Hereinafter, a projector screen according to an embodiment of the disclosure will be described in detail with reference to the accompanying drawings.
- (22) FIG. 2 is a view illustrating a display apparatus **200** including a projector screen **1** according to an embodiment of the disclosure.
- (23) Referring to FIG. 2, a display apparatus **200** may include a projector **201** and a projector screen **1** according to an embodiment of the disclosure.
- (24) The projector **201** projects image light toward the projector screen **1**. The projector **201** may be positioned below the center in the vertical direction of the projector screen **1**.
- (25) The projector screen **1** reflects image light projected from the projector **201**. The projector screen **1** may be formed to absorb light incident from the upper side and reflect image light projected from the projector **201** disposed at the lower side of the projector screen **1** toward the user.
- (26) Hereinafter, the projector screen **1** according to an embodiment of the disclosure will be described in detail with reference to FIG. 3 and FIG. 4.
- (27) FIG. 3 is a cross-sectional view illustrating a projector screen **1** according to an embodiment of the disclosure. FIG. 4 is a partially enlarged cross-sectional view illustrating a reflector, of reflectors **20**, of a projector screen **1** according to an embodiment of the disclosure.
- (28) Referring to FIG. 3, the projector screen **1** according to an embodiment of the disclosure may include a light absorbing layer **10**, a plurality of reflectors **20**, and a transparent layer **30**.
- (29) The light absorbing layer **10** is a layer that absorbs incident light and may be formed of a black

resin film. For example, a black polyethylene terephthalate (PET) film may be used as the light absorbing layer **10**.

(30) The rear surface of the light absorbing layer **10** may form the rear surface **3** of the projector screen **1**.

(31) The plurality of reflectors **20** may be formed to reflect incident light toward the user. For example, the plurality of reflectors **20** may be formed to reflect light incident from the lower side in a direction perpendicular to the front surface **2** of the projector screen **1**. Here, the lower side refers to a place lower than the center in the vertical direction of the projector screen **1**.

(32) The plurality of reflectors **20** may be disposed on the front surface of the light absorbing layer **10** at regular intervals. In other words, the plurality of reflectors **20** are disposed to be spaced apart from each other at regular intervals in the vertical direction of the screen **1**, and the light absorbing layer **10** may be exposed between the plurality of reflectors **20**. The distance d between the plurality of reflectors **20**, that is, the distance between two adjacent reflectors **20** may be set such that image light incident from the projector **201** is reflected by the reflectors **20** without being directly incident on the exposed portions **10a** of the light absorbing layer **10**.

(33) In addition, the plurality of reflectors **20** may be formed to be inclined at a predetermined angle with respect to the light absorbing layer **10**. In other words, the plurality of reflectors **20** may be formed such that the reflective surface **21** that reflects light is inclined at an inclination angle $\theta 1$ with respect to the light absorbing layer **10**. At this time, the inclination angle $\theta 1$ of the reflective surface **21** may be determined to reflect the light incident from the lower side in a direction perpendicular to the front surface **2** of the screen **1**.

(34) For example, each of the plurality of reflectors **20** may be formed in a column shape having a cross-section of a right triangle. The inclined surface of the reflector **20** forms the reflective surface **21** that reflects image light projected from the projector **201** (see FIG. 2), and the rear surface **22** of the reflectors **20** may be attached to the light absorbing layer **10**.

(35) The reflective surface **21** may be formed to be inclined upward with respect to the light absorbing layer **10**. In other words, the reflective surface **21** may be formed to form an obtuse angle with respect to the light absorbing layer **10**.

(36) The amount of light reflection that the reflective surfaces **21** of the plurality of reflectors **20** reflect image light incident from the lower side to the front of the screen **1** may vary according to the inclination angle $\theta 1$ of the reflective surfaces **21**. In the case of this embodiment, when the ratio of the base of the reflective surface **21** to the height of the reflective surface **21** is 0.5 or more, an appropriate amount of reflection may be obtained.

(37) Referring to FIG. 4, the base of the reflective surface **21** refers to the length x of the lower surface **22** of the reflector **20** that contacts the light absorbing layer **10**, and the height of the reflective surface **21** refers to the height y from the light absorbing layer **10** to the highest point of the reflective surface **21**. Accordingly, the reflective surface **21** of the reflector **20** may have an ideal optical structure when $x/y \geq 0.5$.

(38) On the other hand, the ratio of the base x of the reflective surface **21** to the height y of the reflective surface **21** may be 5 or less.

(39) The plurality of reflectors **20** may be formed of a material that reflects light. For example, the plurality of reflectors **20** may be formed of white beads. White beads may be formed of fine grains formed of titanium dioxide TiO_2 or silicon dioxide SiO_2 . As another example, the plurality of reflectors **20** may be formed of white resin.

(40) The transparent layer **30** is disposed on the upper side of the plurality of reflectors **20**, and the upper side of the plurality of reflectors **20** may be formed as a flat surface by the transparent layer **30**.

(41) The transparent layer **30** may be formed of a material that transmits light. Accordingly, image light projected from the projector may pass through the transparent layer **30** and be reflected by the reflective surfaces **21** of the plurality of reflectors **20**, and external light may pass through the

transparent layer **30** and be absorbed by the light absorbing layer **10**.

(42) The transparent layer **30** may include a front surface **31** formed in a flat surface parallel to the light absorbing layer **10** and a rear surface **32** formed with a plurality of grooves **33** (see FIG. 6B) and attached to the light absorbing layer **10**. The rear surface **32** of the transparent layer **30** may be formed parallel to the front surface **31**, and the plurality of grooves **33** may be formed in a shape corresponding to the plurality of reflectors **20**.

(43) For example, when the plurality of reflectors **20** are formed in the shape of columns having a cross-section of a right triangle, the plurality of grooves **33** may be formed as grooves having a cross-section of a right triangle into which the right triangle columns are inserted. In other words, each of the plurality of grooves **33** may be formed as a groove having a right triangle shape having an inclined surface **34** and a side surface **35**.

(44) Therefore, when the plurality of reflectors **20** are inserted into the plurality of grooves **33** of the transparent layer **30**, the inclined surfaces of the reflectors **20**, that is, the reflective surfaces **21** and the side surfaces **23** come into close contact with the inclined surfaces **34** and the side surfaces **35** of the grooves **33** of the transparent layer **30**, respectively. As such, the rear surface **32** of the transparent layer **30** comes into contact with the portions **10a** of the light absorbing layer **10** exposed between the plurality of reflectors **20**.

(45) Therefore, the transparent layer **30** may be disposed on the front surface of the light absorbing layer **10** while covering the plurality of reflectors **20**.

(46) The transparent layer **30** may be formed of a transparent urethane resin. The plurality of grooves **33** of the transparent layer **30** may be formed using an imprinting method.

(47) A base film **40** may be disposed on the front surface of the transparent layer **30**. The base film **40** may be formed of a transparent material through which light may pass. For example, the base film **40** may be formed of a transparent polyethylene terephthalate (PET) film.

(48) In addition, a low reflection layer **50** may be disposed on the front surface of the base film **40**. The low reflection layer **50** may be formed to reduce light reflectance on the front surface **2** of the projector screen **1**. Accordingly, when the low reflection layer **50** is disposed on the front surface **2** of the projector screen **1**, reflection of external light felt by the viewer may be reduced.

(49) The low reflection layer **50** may be formed of a transparent material through which light passes, and may be formed in the form of a thin film. For example, the low reflection layer **50** may be formed integrally with the base film **40**.

(50) In the projector screen **1** according to an embodiment illustrated in FIG. 3, the low reflection layer **50** is disposed on the front surface of the base film **40**. However, the disclosure is not limited thereto. The low reflection layer **50** may be selectively disposed on the projector screen **1**. In other words, in the projector screen **1** according to another example, the low reflection layer **50** may not be disposed on the front surface of the base film **40**.

(51) Hereinafter, a light path in the projector screen **1** according to an embodiment of the disclosure having the above-described structure will be described in detail with reference to FIG. 5.

(52) FIG. 5 is a view illustrating paths of image light **L** and external light **G** incident on a projector screen **1** according to an embodiment of the disclosure.

(53) Referring to FIG. 5, external light **G** is incident from the upper side of the projector screen **1** toward the front surface **2** of the projector screen **1**. The external light **G** refers to light emitted from lighting disposed on the ceiling of the room.

(54) External light **G** passes through the low reflection layer **50**, the base film **40**, and the transparent layer **30**, and then enters the light absorbing layer **10**. The light absorbing layer **10** is formed of a black resin film to absorb light. The external light **G** incident on the light absorbing layer **10** is absorbed by the light absorbing layer **10** and is not reflected to the front surface **2** of the projector screen **1**.

(55) Image light **L** projected from the projector **201** (see FIG. 2) disposed below the projector screen **1** is incident toward the front surface **2** of the projector screen **1**.

(56) The image light L projected from the projector **201** passes through the low reflection layer **50**, the base film **40**, and the transparent layer **30**, and then is incident on the reflective surface **21** of each of the plurality of reflectors **20**. The image light L incident on the reflective surface **21** is reflected by the reflective surface **21**, passes through the transparent layer **30**, the base film **40**, and the low reflection layer **50**, and then is emitted in a direction perpendicular to the front surface **32** of the projector screen **1**, that is, the low reflection layer **50**. The viewer may see the image light L reflected by the reflective surfaces **21** of the plurality of reflectors **20**.

(57) Because the projector screen **1** according to an embodiment of the disclosure having the above-described structure may lower the black level in a bright room and reflect the image light L projected from the projector **201** as much as possible, the bright-room contrast ratio may be improved. Accordingly, the image quality perceived by the viewer may be improved.

(58) Hereinafter, a method of manufacturing the projector screen **1** according to an embodiment of the disclosure as described above will be described in detail with reference to FIG. **6A**, FIG. **6B**, FIG. **6C**, FIG. **6D**, and FIG. **6E**.

(59) FIG. **6A**, FIG. **6B**, FIG. **6C**, FIG. **6D**, and FIG. **6E** are views for explaining a method of manufacturing a projector screen **1** according to an embodiment of the disclosure.

(60) First, the base film **40** is prepared. The base film **40** may be formed of a rectangular transparent sheet having a thin thickness. The base film **40** may be formed of a transparent polyethylene terephthalate (PET) film.

(61) Next, as illustrated in FIG. **6A**, a transparent layer **30** is formed on a surface of the base film **40**. The transparent layer **30** may be a transparent urethane layer formed of a transparent urethane resin. The transparent layer **30** may be attached to the base film **40** so as not to be separated. In other words, the transparent layer **30** may be formed in a layered structure over the entire surface of the base film **40**.

(62) Subsequently, as illustrated in FIG. **6B**, a plurality of grooves **33** are formed at regular intervals on the upper surface of the transparent layer **30**. The plurality of grooves **33** may be formed to have a cross-section of a right triangle. Accordingly, the groove **33** having a right triangle shape may include a side surface **35** perpendicular to the base film **40** and an inclined surface **34** inclined at an inclination angle $\theta 2$ with respect to the base film **40**.

(63) The inclined surface **34** of the right triangular groove **33** may form an acute angle with respect to the base film **40**. For example, the right triangular groove **33** may be formed such that the ratio of the width of the upper surface of the groove **33**, that is, the width w of the opening **36** of the groove **33** to the height h of the groove **33**, that is, the length of the side surface **34** of the groove **33** is 0.5 or more. The height h of the groove **33** and the width w of the opening of the groove **33** correspond to the height y of the reflective surface **21** and the base x of the reflective surface **21** described above, respectively.

(64) The inclined surfaces **34** and the side surfaces **35** of the two adjacent right triangular grooves **33** may be formed to be spaced apart from each other by a predetermined distance. In other words, the inclined surfaces **34** and the side surfaces **35** of the two adjacent right triangular grooves **33** may be formed so as not to contact each other.

(65) The plurality of right triangular grooves **33** may be formed through an imprinting process. For example, the plurality of right triangular grooves **33** may be formed on the upper surface of the transparent layer **30** using an imprinting jig in which a plurality of right triangle protrusions are arranged in parallel at regular intervals.

(66) Next, as illustrated in FIG. **6C**, the plurality of grooves **33** of the transparent layer **30** are filled with white beads **20a**. The white beads **20a** filled in the plurality of grooves **33** of the transparent layer **30** may form the reflectors **20**.

(67) The white beads **20a** may be particles formed of titanium dioxide TiO_2 or silicon dioxide SiO_2 . The white beads **20a** may be fixed to the plurality of grooves **33** of the transparent layer **30** using a binder or the like.

(68) As another example, the plurality of reflectors **20** may be formed by filling the plurality of grooves **33** of the transparent layer **30** with white resin. The white resin refers to a resin having a white color so as to reflect light.

(69) Subsequently, as illustrated in FIG. **6D**, a light absorbing layer **10** is disposed on the upper surface of the transparent layer **30** in which the plurality of grooves **33** are formed. The light absorbing layer **10** may be disposed to cover the entire surface of the transparent layer **30**.

Accordingly, the white beads filled in the plurality of grooves **33** of the transparent layer **30**, and, the reflectors **20** may also be covered by the light absorbing layer **10**.

(70) An adhesive may be applied between the upper surface of the transparent layer **30** and the light absorbing layer **10** to fix the light absorbing layer **10** to the upper surface of the transparent layer **30**.

(71) The light absorbing layer **10** may be formed of a black resin film to absorb incident light. For example, the light absorbing layer **10** may be formed of a black polyethylene terephthalate (PET) film. The light absorbing layer **10** forms the rear surface **3** of the projector screen **1**.

(72) Finally, as illustrated in FIG. **6E**, a low reflection layer **50** is formed on the lower surface of the base film **40**. In other words, the low reflection layer **50** may be formed on the other surface of the base film **40** on which the transparent layer **30** is not formed.

(73) In this embodiment, the low reflection layer **50** is formed on the lower surface of the base film **40** in the final operation, but the disclosure is not limited thereto. As another embodiment, when preparing the base film **40** as the first operation, the low reflection layer **50** may be formed on a surface of the base film **40**.

(74) In the above, the case where the projector screen **1** includes the low reflection layer **50** has been described. However, the projector screen **1** may not include the low reflection layer **50**. In this case, the operation of forming the low reflection layer **50** on the lower surface of the base film **40** described above is not required.

(75) As described above, according to the method of manufacturing the projector screen **1** according to an embodiment of the disclosure, unlike screens according to the related art, it is not necessary to form the reflective surfaces in fine triangular patterns by sputtering or by coating white ink, so manufacturing costs may be reduced.

(76) In another embodiment, a color absorption layer **60** may be disposed on the projector screen **1**. For example, as illustrated in FIG. **7**, the color absorption layer **60** may be provided on the front surface of the low reflection layer **50** of the projector screen **1**.

(77) FIG. **7** is a cross-sectional view illustrating a projector screen **1** according to an embodiment of the disclosure.

(78) An absorption layer **10**, a plurality of reflectors **20**, a transparent layer **30**, a base film **40**, and a low reflection layer **50** of the projector screen **1** according to the embodiment illustrated in FIG. **7** are the same as those of the projector screen **1** as illustrated in FIG. **3**; therefore, detailed descriptions thereof are omitted.

(79) The color absorption layer **60** may be formed over the entire front surface of the low reflection layer **50** to have a predetermined thickness on the front surface of the low reflection layer **50**.

(80) The color absorption layer **60** may be formed to absorb light having a predetermined wavelength. The color absorption layer **60** may be formed using a color absorbing dye. For example, the color absorbing dye may be formed of Tetra-Aza-Porphyrin (TAP). The color absorbing dye may be formed to absorb a specific color light among various color lights included in light. In other words, the color absorbing dye may be formed to absorb light having a specific range of wavelengths among visible light.

(81) FIG. **8** is a graph illustrating an absorption spectrum for each wavelength band of light. In FIG. **8**, the horizontal axis represents the wavelength (nm) of light, and the vertical axis represents absorbance.

(82) FIG. **8** shows a case in which six wavelength bands, that is, six color lights, are absorbed using

six color absorbing dyes. For example, in FIG. 8, the curve **801** represents a case where blue light is absorbed by a color absorbing dye capable of absorbing blue light, the curve **802** represents a case where yellow light is absorbed by a color absorbing dye capable of absorbing yellow light, and the curve **803** represents a case where orange light is absorbed by a color absorbing dye capable of absorbing orange light.

(83) The color absorption layer **60** of the projector screen **1** according to this embodiment may be formed of a color absorbing dye capable of absorbing yellow light. Then, the yellow light included in the external light incident on the projector screen **1** may be absorbed. A result that the projector screen **1** including the color absorption layer **60** as illustrated in FIG. 7 absorbs the yellow light of the incident external light is shown in FIG. 9.

(84) FIG. 9 is a graph comparing light intensity of a projector screen **1** including a color absorbing layer **60** capable of absorbing yellow light and light intensity of a projector screen **1** without a color absorbing layer **60**. In FIG. 9, the horizontal axis represents the wavelength (nm) of external light, and the vertical axis represents the intensity of light.

(85) In FIG. 9, the curve **901** represents the intensity of light measured on the projector screen **1** including the color absorption layer **60** capable of absorbing yellow light, and the curve **902** represents the intensity of light measured on the projector screen **1** without the color absorption layer **60**.

(86) Referring to FIG. 9, the intensity of external light decreases in a wavelength region of 590 nm (arrow) corresponding to yellow light. When yellow light of external light is absorbed using the color absorption layer **60** in this way, the contrast ratio in a bright room condition may be improved.

(87) In this case, because the projector **201** emits red light, green light, and blue light as illustrated in FIG. 10, there is no interference with the color absorption layer **60** of the projector screen **1** that absorbs yellow light.

(88) FIG. 10 is a graph illustrating a spectrum of image light projected from a projector **201**. In FIG. 10, the horizontal axis represents the wavelength (nm) of light, and the vertical axis represents the intensity of light. Further, in FIG. 10, the straight line **1001** represents blue light emitted from the projector **201**, the straight line **1002** represents green light emitted from the projector **201**, and the straight line **1003** represents red light emitted from the projector **201**.

(89) Referring to FIG. 10, the projector **201** emits blue light, green light, and red light, and does not emit the wavelength of yellow light (about 590 nm) absorbed by the color absorption layer **60** of the projector screen **1**, so that the image light L emitted from the projector **201** is not absorbed by the color absorption layer **60**.

(90) Hereinafter, a projector screen **1'** according to another embodiment of the disclosure will be described in detail with reference to FIG. 11 and FIG. 12.

(91) FIG. 11 is a cross-sectional view illustrating a projector screen **1'** according to an embodiment of the disclosure. FIG. 12 is a partially enlarged cross-sectional view illustrating a reflector, of reflectors **20'**, of a projector screen **1'** according to an embodiment of the disclosure.

(92) Referring to FIG. 11, the projector screen **1'** according to an embodiment of the disclosure may include a light absorbing layer **10**, a plurality of reflectors **20'**, and a transparent layer **30**.

(93) The light absorbing layer **10** is a layer that absorbs incident light. A black resin film may be used as the light absorbing layer **10**. For example, a black polyethylene terephthalate (PET) film may be used as the light absorbing layer **10**.

(94) The plurality of reflectors **20'** may be formed to reflect incident light toward the user. For example, the plurality of reflectors **20'** may be formed to reflect light incident from the lower side in a direction perpendicular to the front surface **2** of the projector screen **1'**. Here, the lower side refers to a place lower than the center in the vertical direction of the projector screen **1'**.

(95) The plurality of reflectors **20'** may be disposed on the front surface of the light absorbing layer **10** at regular intervals. In other words, the plurality of reflectors **20'** are disposed to be spaced apart

from each other at regular intervals in the vertical direction of the projector screen **1'**, and the light absorbing layer **10** may be exposed between the plurality of reflectors **20'**. At this time, the distance d' between the plurality of reflectors **20'**, that is, the distance between two adjacent reflectors **20'** may be determined such that image light incident from the projector **201** is reflected by the reflectors **20'** without being directly incident on the exposed portions **10a** of the light absorbing layer **10**.

(96) In addition, the plurality of reflectors **20'** may be formed to be inclined at a predetermined angle with respect to the light absorbing layer **10**. In other words, the plurality of reflectors **20'** may be formed such that the reflective surface **21** that reflects light is inclined at an inclination angle $\theta 1$ with respect to the light absorbing layer **10**. At this time, the inclination angle $\theta 1$ of the reflective surface **21** may be determined to reflect the light incident from the lower side in a direction perpendicular to the front surface **2** of the projector screen **1'**.

(97) For example, each of plurality of reflectors **20'** may be formed in a flat plate shape having a trapezoidal cross-section. The inclined surface of the reflector **20'** forms the reflective surface **21** that reflects image light projected from the projector **201**, and one surface **27** of the reflector **20'** may be fixed to the light absorbing layer **10**. The reflective surface **21** may be formed to be inclined upward with respect to the light absorbing layer **10**. In other words, the reflective surface **21** may be formed to form an obtuse angle with respect to the light absorbing layer **10**.

(98) As illustrated in FIG. **11**, when the cross-section of the reflector **20'** is formed in a trapezoid, the reflector **20'** may include two inclined surfaces, lower inclined surface **25** and inclined surface **26**, parallel to each other and inclined with respect to the light absorbing layer **10**, and a front surface **28** and a rear surface **27** connecting the front and rear ends of the two inclined surfaces, lower inclined surface **25** and inclined surface **26**. Among the two inclined surfaces, lower inclined surface **25** and inclined surface **26**, parallel to each other, the lower inclined surface **25** forms the reflective surface **21** that reflects image light projected from the projector **201**. The rear surface **27** of the reflector **20'** forming the side of the trapezoid may contact the light absorbing layer **10**.

(99) The amount of light reflection that the reflective surfaces **21** of the plurality of reflectors **20'** reflect image light incident from the lower side to the front may vary according to the inclination of the reflective surfaces **21**. In this case, when the ratio of the base of the reflective surface **21** to the height of the reflective surface **21** is 0.5 or more, an appropriate amount of light reflection may be obtained.

(100) Referring to FIG. **12**, the height y of the reflective surface **21** refers to the height from the light absorbing layer **10** to the highest point **P** of the reflective surface **21**, and the base x of the reflective surface **21** refers to the distance from the lower end **Q** of the reflective surface **21** in contact with the light absorbing layer **10** to a point **R** at which an imaginary straight line drawn perpendicular to the light absorbing layer **10** from the highest point **P** of the reflective surface **21** intersects the light absorbing layer **10**.

(101) Accordingly, the reflective surface **21** of the reflector **20'** may have an ideal optical structure when $x/y \geq 0.5$.

(102) On the other hand, the ratio of the base x of the reflective surface **21** to the height y of the reflective surface **21** may be 5 or less.

(103) The plurality of reflectors **20'** may be formed of a material that reflects light. For example, the plurality of reflectors **20'** may be formed of white beads. White beads may be formed of fine grains formed of titanium dioxide TiO_2 or silicon dioxide SiO_2 . Alternatively, the plurality of reflectors **20'** may be formed of white resin.

(104) The transparent layer **30** is disposed on the upper side of the plurality of reflectors **20'**, and the upper side of the plurality of reflectors **20'** may be formed as a flat surface by the transparent layer **30**. The transparent layer **30** may be formed of a material that transmits light. Accordingly, image light may pass through the transparent layer **30** and be reflected by the reflective surfaces **21** of the plurality of reflectors **20'**, and external light may pass through the transparent layer **30** and be

absorbed by the light absorbing layer **10**.

(105) The transparent layer **30** may include a front surface **31** formed in a flat surface parallel to the light absorbing layer **10** and a rear surface **32** formed with a plurality of grooves **33'** and attached to the light absorbing layer **10**. The rear surface **32** of the transparent layer **30** may be formed parallel to the front surface **31**, and the plurality of grooves **33'** may be formed in a shape corresponding to the plurality of reflectors **20'**.

(106) For example, when the plurality of reflectors **20'** are formed in a flat plate having a trapezoidal cross-section, the plurality of grooves **33'** may be formed as grooves having a trapezoidal cross-section into which the flat plate having the trapezoidal cross-section is inserted. In other words, each of the plurality of grooves **33'** may be formed as a trapezoid-shaped groove having two inclined surfaces, inclined surface **27** and inclined surface **38**, inclined with respect to the rear surface **32** of the transparent layer **30** and parallel to each other and a bottom surface **39** connecting lower ends of the two inclined surfaces, inclined surface **27** and inclined surface **38**.

(107) Therefore, when the plurality of reflectors **20'** are inserted into the plurality of grooves **33'** of the transparent layer **30**, the two inclined surfaces, lower inclined surface **25** and inclined surface **26**, and the front surface **28** of the reflectors **20'** come into close contact with the two inclined surfaces, inclined surface **37** and inclined surface **38**, and the bottom surface **39** of the grooves **33'** of the transparent layer **30**, respectively. At this time, the rear surface **32** of the transparent layer **30** comes into contact with the light absorbing layer **10**.

(108) Therefore, the transparent layer **30** may be disposed on the upper surface of the light absorbing layer **10** while covering the plurality of reflectors **20'**.

(109) The transparent layer **30** may be formed of a transparent urethane resin. The plurality of grooves **33'** of the transparent layer **30** may be formed using an imprinting process and a roller plastic process.

(110) A base film **40** may be disposed on the front surface **31** of the transparent layer **30**. The base film **40** may be formed of a transparent material through which light may pass. For example, the base film **40** may be formed of a transparent polyethylene terephthalate (PET) film.

(111) In addition, a low reflection layer **50** may be disposed on the front surface of the base film **40**. The low reflection layer **50** may be formed to reduce the reflectance of light on the front surface **2** of the projector screen **1'**. Accordingly, when the low reflection layer **50** is disposed on the front surface **2** of the projector screen **1'**, reflection of external light felt by the viewer may be reduced.

(112) The low reflection layer **50** may be formed of a transparent material through which light passes, and may be formed in the form of a thin film. For example, the low reflection layer **50** may be formed integrally with the base film **40**.

(113) In the projector screen **1'** according to an embodiment illustrated in FIG. **11**, the low reflection layer **50** is disposed on the front surface of the base film **40**. However, the structure of the projector screen **1'** is not limited thereto. The projector screen **1'** according to the embodiments may optionally include the low reflection layer **50**. In other words, in the projector screen **1'** according to another example, the low reflection layer **50** may not be disposed on the front surface of the base film **40**.

(114) Hereinafter, a light path in the projector screen **1'** according to an embodiment of the disclosure having the above-described structure will be described in detail.

(115) FIG. **13** is a view illustrating light paths of image light and external light incident on a projector screen according to an embodiment of the disclosure.

(116) Referring to FIG. **13**, external light is incident from the upper side of the projector screen **1'** toward the front surface **2** of the projector screen **1'**.

(117) External light passes through the low reflection layer **50**, the base film **40**, and the transparent layer **30**, and then enters the light absorbing layer **10**. The light absorbing layer **10** is formed of a black resin film to absorb light. Therefore, the external light incident on the light absorbing layer

10 is absorbed by the light absorbing layer **10** and is not reflected to the front surface **2**.

(118) Image light **L** projected from the projector **201** (see FIG. 2) disposed below the projector screen **1'** is incident toward the front surface **2** of the projector screen **1'**.

(119) The image light **L** projected from the projector **201** passes through the low reflection layer **50**, the base film **40**, and the transparent layer **30**, and then is incident on the reflective surface **21** of each of the plurality of reflectors **20'**. The image light **L** incident on the reflective surface **21** is reflected by the reflective surface **21**, passes through the transparent layer **30**, the base film **40**, and the low reflection layer **50**, and then is emitted in a direction perpendicular to the front surface **2** of the projector screen **1'**, that is, the low reflection layer **50**. The viewer may see the image light **L** reflected by the reflective surfaces **21** of the plurality of reflectors **20'**.

(120) Because the projector screen **1'** according to an embodiment of the disclosure having the above-described structure may lower the black level in a bright room and maximally reflect the image light **L** projected from the projector **201**, the bright-room contrast ratio may be improved. Accordingly, the image quality perceived by the viewer may be improved.

(121) Hereinafter, a method of manufacturing the projector screen **1'** according to an embodiment of the disclosure as described above will be described in detail with reference to FIG. 14A, FIG. 14B, FIG. 14C, FIG. 14D, FIG. 14E, and FIG. 14F.

(122) FIG. 14A, FIG. 14B, FIG. 14C, FIG. 14D, FIG. 14E, and FIG. 14F are views for explaining a method of manufacturing a projector screen **1'** according to an embodiment of the disclosure.

(123) First, the base film **40** is prepared. The base film **40** may be formed of a rectangular transparent sheet having a thin thickness. The base film **40** may be formed of a transparent polyethylene terephthalate (PET) film.

(124) Next, as illustrated in FIG. 14A, a transparent layer **30** is formed on a surface of the base film **40**. The transparent layer **30** may be a transparent urethane layer formed of a transparent urethane resin. The urethane layer **30** may be attached to the base film **40** so as not to be separated. In other words, the base film **40** and the transparent layer **30** may form a layered structure. In addition, the transparent layer **30** may be formed with the same area as the base film **40**.

(125) Subsequently, as illustrated in FIG. 14B, a plurality of grooves **33'** are formed at regular intervals from each other on the upper surface of the transparent layer **30**. The plurality of grooves **33'** may be formed to have a rectangular cross-section. The plurality of rectangular shaped grooves **33'** may be formed perpendicular to the base film **40**. At this time, each of the plurality of grooves **33'** having a rectangular cross section may be formed to have a depth greater than a width.

(126) The plurality of grooves **33'** having a rectangular cross-section may be formed through an imprinting process. For example, the plurality of grooves **33'** having a rectangular shape may be formed on the upper surface of the transparent layer **30** using an imprinting jig in which a plurality of protrusions having a rectangular cross section are arranged in parallel at regular intervals.

(127) Next, as illustrated in FIG. 14C, the plurality of grooves **33'** of the transparent layer **30** are filled with white beads **20a**. The white beads **20a** filled in the plurality of grooves **33'** of the transparent layer **30** may form the reflectors **20'**.

(128) The white beads **20a** may be grains formed of titanium dioxide TiO_2 or silicon dioxide SiO_2 . The white beads **20a** may be fixed to the plurality of grooves **33'** of the transparent layer **30** using a binder or the like.

(129) As another example, the plurality of reflectors **20'** may be formed by filling the plurality of grooves **33'** of the transparent layer **30** with a white resin. The white resin refers to a resin having a white color so as to reflect light.

(130) Subsequently, as illustrated in FIG. 14D, the transparent layer **30** is molded by using a roller **70** so that the plurality of grooves **33'** having a rectangular cross-section of the transparent layer **30** are inclined at an inclination angle θ_2 with respect to the base film **40**.

(131) The transparent layer **30** is formed of a transparent urethane resin having a soft property. Therefore, when the base film **40** to which the lower surface of the transparent layer **30** is fixed is

fixed and the upper end of the transparent layer **30** is pressed in one direction using the roller **70**, the upper end of the transparent layer **30** moves a certain distance relative to the lower end, so that the transparent layer **30** is transformed. At this time, the plurality of grooves **33'** having a rectangular cross-section are inclined at an inclination angle $\theta 2$ with respect to the base film **40**. When the transparent layer **30** is cured in this state, the plurality of grooves **33'** having a rectangular cross-section may maintain an inclined state with respect to the base film **40**.

(132) In this case, because the reflectors **20'** filled with the white beads **20a** are formed in the plurality of grooves **33'** having a rectangular cross-section, the reflectors **20'** are inclined at a predetermined angle with respect to the base film **40**. The reflectors **20'** of the molded transparent layer **30** may form an acute angle $\theta 2$ with respect to the base film **40**.

(133) In addition, in the operation of forming the transparent layer **30** to be inclined, the groove **33'** having a rectangular cross-section may be molded such that the ratio of the base x of an inclined side to the height y of the inclined side is 0.5 or more. When the transparent layer **30** is molded in this way, the ratio of the base x of the reflective surface **21** to the height y of the reflective surface **21** in the reflectors **20'** formed in the grooves **33'** having a rectangular cross-section may be greater than 0.5.

(134) Next, as illustrated in FIG. **14E**, a light absorbing layer **10** is disposed on the upper surface of the transparent layer **30** in which the plurality of reflectors **20'** are formed.

(135) An adhesive may be applied between the upper surface of the transparent layer **30** and the light absorbing layer **10** to fix the light absorbing layer **10** to the upper surface of the transparent layer **30**. After the above-described molding process of the transparent layer **30** is completed, when the upper surface of the transparent layer **30** is not flat, the light absorbing layer **10** may be attached to the upper surface of the transparent layer **30** by using an adhesive.

(136) The light absorbing layer **10** may be formed of a black resin film to absorb incident light. For example, the light absorbing layer **10** may be formed of a black polyethylene terephthalate (PET) film. The light absorbing layer **10** forms the rear surface **3** of the projector screen **1'**.

(137) Finally, as illustrated in FIG. **14F**, a low reflection layer **50** is formed on the lower surface of the base film **40**. In other words, the low reflection layer **50** may be formed on the other surface of the base film **40** on which the transparent layer **30** is not formed.

(138) In this embodiment, the low reflection layer **50** is formed on the lower surface of the base film **40** in the final operation, but the disclosure is not limited thereto. As another embodiment, when preparing the base film **40** as the first operation, the low reflection layer **50** may be formed on a surface of the base film **40**.

(139) In the above, the case where the projector screen **1'** includes the low reflection layer **50** has been described. However, the projector screen **1'** may not include the low reflection layer **50**. In this case, the operation of forming the low reflection layer **50** on the lower surface of the base film **40** described above is not required according to an embodiment.

(140) As described above, according to the method of manufacturing the projector screen **1'** according to an embodiment of the disclosure, unlike screens according to the related art, it is not necessary to form the reflective surfaces in fine triangular patterns by sputtering or by coating white ink, so manufacturing costs may be reduced.

(141) In another embodiment, a color absorption layer **60** may be disposed on the projector screen **1'**. For example, as illustrated in FIG. **15**, the color absorption layer **60** may be provided on the front surface of the low reflection layer **50** of the projector screen **1'**.

(142) FIG. **15** is a cross-sectional view illustrating a projector screen according to an embodiment of the disclosure.

(143) An absorption layer **10**, a plurality of reflectors **20'**, a transparent layer **30**, a base film **40**, and a low reflection layer **50** of the projector screen **1'** according to the embodiment illustrated in FIG. **15** are the same as those of the projector screen **1'** as illustrated in FIG. **11**; therefore, detailed descriptions thereof are omitted.

(144) The color absorption layer **60** may be formed over the entire front surface of the low reflection layer **50** to have a predetermined thickness on the front surface of the low reflection layer **50**.

(145) The color absorption layer **60** may be formed to absorb light having a predetermined wavelength. The color absorption layer **60** is the same as the color absorption layer **60** of the projector screen **1** shown in FIG. 7; therefore, a detailed description thereof is omitted.

(146) According to one or more embodiments, a projector screen having the above structure may lower a black level in a bright room and reflect image light projected from a projector as much as possible, the bright-room contrast ratio is improved. Accordingly, an image quality perceived by the viewer may be improved.

(147) The embodiments of disclosure described above are examples. The terms used herein are for the purpose of description and should not be construed in a limiting sense. Various modifications and variations of the disclosure are possible according to the above contents. Accordingly, unless otherwise stated, the disclosure may be practiced freely within the scope of the claims.

Claims

1. A projector screen comprising: a light absorbing layer configured to absorb light; a plurality of reflectors provided on a front surface of the light absorbing layer and spaced apart from each other at regular intervals, wherein the plurality of reflectors are inclined with respect to the light absorbing layer and are configured to reflect light; and a transparent layer disposed above the plurality of reflectors and configured to transmit light therethrough, wherein the transparent layer comprises a front surface that is flat and parallel to the light absorbing layer, and a rear surface having a plurality of grooves having a shape corresponding to the plurality of reflectors, wherein the plurality of reflectors are provided in the plurality of grooves of the transparent layer, and the rear surface of the transparent layer contacts the front surface of the light absorbing layer.
2. The projector screen of claim 1, wherein a cross-section of each reflector of the plurality of reflectors has a shape of a right triangle, and wherein each reflector of the plurality of reflectors comprises a rear surface that contacts the light absorbing layer and is a base of the shape of the right triangle.
3. The projector screen of claim 1, wherein a cross-section of each reflector of the plurality of reflectors has a shape of a trapezoid, and wherein each reflector of the plurality of reflectors comprises a rear surface that contacts the light absorbing layer and is a side of the shape of the trapezoid.
4. The projector screen of claim 1, wherein each reflector of the plurality of reflectors comprises a reflective surface inclined with respect to the light absorbing layer and configured to reflect light, and wherein a ratio of a base of the reflective surface to a height of the reflective surface is at least 0.5.
5. The projector screen of claim 1, wherein the plurality of reflectors comprise white beads.
6. The projector screen of claim 1, wherein the transparent layer comprises a transparent urethane resin.
7. The projector screen of claim 1, further comprising: a base film that is disposed on the front surface of the transparent layer and is transparent.
8. The projector screen of claim 7, further comprising: a low reflection layer disposed on a front surface of the base film.
9. The projector screen of claim 8, further comprising: a color absorption layer disposed on a front surface of the low reflection layer.
10. The projector screen according to claim 1, wherein the front surface of the transparent layer is parallel to the flat surface of the light absorbing layer and separate from all of the plurality of reflectors.

11. The projector screen according to claim 1, wherein the front surface of the light absorbing layer is a flat surface that is in contact with the rear surface of the transparent layer and each of the plurality of reflectors.
 12. The projector screen according to claim 11, wherein each reflector of the plurality of reflectors comprises a reflective surface inclined with respect to the light absorbing layer and configured to reflect light, and wherein a ratio of a base of the reflective surface to a height of the reflective surface is at least 0.5.
 13. A method of manufacturing a projector screen, the method comprising: forming a transparent layer on a first surface of a base film; forming a plurality of grooves on an upper surface of the transparent layer, wherein each groove of the plurality of grooves has a right triangle cross-section and the plurality of grooves are spaced apart from each other at regular intervals; filling the plurality of grooves with at least one of white beads or white resin; and disposing a light absorbing layer on the upper surface of the transparent layer in which the plurality of grooves are formed.
 14. The method of claim 13, wherein each groove of the plurality of grooves has a ratio of an opening width to a height is at least 0.5.
 15. The method of claim 13, wherein the forming the plurality of grooves on the upper surface of the transparent layer comprises forming the plurality of grooves on the upper surface of the transparent layer by performing an imprinting process.
 16. The method of claim 13, further comprising: forming a low reflection layer on a second surface of the base film that is different than the first surface; and forming a color absorption layer on a surface of the low reflection layer that does not contact with the base film.
 17. A method of manufacturing a projector screen, the method comprising: forming a transparent layer on a surface of a base film; forming a plurality of grooves on an upper surface of the transparent layer, wherein each groove of the plurality of grooves has a rectangular cross-section and the plurality of grooves are spaced apart from each other at regular intervals; filling the plurality of grooves with white beads; molding the transparent layer by using a roller such that the plurality of grooves filled with the white beads are inclined with respect to the base film; and disposing a light absorbing layer on the upper surface of the transparent layer molded by the roller.
 18. The method of claim 17, wherein each groove of the plurality of grooves having a rectangular cross-section inclined in the molding the transparent layer is formed so that a ratio of a base of an inclined side to a height of the inclined side is at least 0.5.
-