

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12415262
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Shinkawa; Akira

Secondary battery, battery pack, electronic device, electric tool, electric aircraft, and electric vehicle

Abstract

Provided is a secondary battery, where a positive electrode includes a first covered part covered with a positive electrode active material layer and a positive electrode active material non-covered part on a positive electrode foil, and a negative electrode includes a second covered part covered with a negative electrode active material layer and a negative electrode active material non-covered part on a negative electrode foil, the positive electrode active material non-covered part is joined to a positive electrode current-collecting plate at one end of the electrode wound body, and the negative electrode active material non-covered part is joined to a negative electrode current-collecting plate at the other end of the electrode wound body.

Inventors:	Shinkawa; Akira (Kyoto, JP)
Applicant:	MURATA MANUFACTURING CO., LTD. (Kyoto, JP)
Family ID:	1000008819953
Assignee:	MURATA MANUFACTURING CO., LTD. (Kyoto, JP)
Appl. No.:	17/580958
Filed:	January 21, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220149489 A1	May. 12, 2022

Foreign Application Priority Data

JP	2019-139815	Jul. 30, 2019
----	-------------	---------------

Related U.S. Application Data

Publication Classification

Int. Cl.: B25F5/00 (20060101); B64C27/00 (20060101); B64D27/34 (20240101); B64D27/357 (20240101); B64U50/30 (20230101); H01M10/0587 (20100101); H01M50/531 (20210101); B64U10/16 (20230101); B64U30/20 (20230101)

U.S. Cl.:

CPC B25F5/00 (20130101); B64C27/00 (20130101); B64D27/34 (20240101); B64D27/357 (20240101); B64U50/30 (20230101); H01M10/0587 (20130101); H01M50/531 (20210101); B64U10/16 (20230101); B64U30/20 (20230101); H01M2220/20 (20130101); H01M2220/30 (20130101)

Field of Classification Search

CPC: H01M (10/0587); H01M (50/531); B25F (5/00); B64D (27/34); B64D (27/357)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2005/0271933	12/2004	Matsumoto et al.	N/A	N/A
2006/0024572	12/2005	Lee	429/161	H01M 10/0431
2015/0072204	12/2014	Kwon	429/94	H01M 50/538
2018/0351212	12/2017	Matsui et al.	N/A	N/A
2020/0203678	12/2019	Shinoda et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2006012801	12/2005	JP	N/A
2006032112	12/2005	JP	N/A
2008166030	12/2007	JP	H01M 10/04
2018206514	12/2017	JP	N/A
2019061851	12/2018	JP	N/A

OTHER PUBLICATIONS

International Search Report of corresponding PCT application PCT/JP2020/028457, dated Oct. 20, 2020. cited by applicant
Japanese Office Action issued Oct. 4, 2022 in corresponding Japanese Application No. 2021-536999. cited by applicant
Chinese Office Action issued Nov. 29, 2023 in corresponding Chinese Application No. 202080053618.8. cited by applicant

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS (1) The present application is a continuation of PCT patent application no. PCT/JP2020/028457, filed on Jul. 22, 2020, which claims priority to Japanese patent application no. JP2019-139815 filed on Jul. 30, 2019, the entire contents of which are being incorporated herein by reference.

BACKGROUND

(1) The present disclosure generally relates to a secondary battery, a battery pack, an electronic device, an electric tool, an electric aircraft, and an electric vehicle.

(2) High-power batteries are required for automobiles, machines, tools, and the like. As a method for producing high power, high-rate discharge for the flow of a relatively large current from a battery has been proposed. The high-rate discharge has a problem with the internal resistance of the battery, because of the flow of the large current.

SUMMARY

(3) The present disclosure generally relates to a secondary battery, a battery pack, an electronic device, an electric tool, an electric aircraft, and an electric vehicle.

(4) The conventional battery may have a problem of failing to achieve welding in some cases.

(5) Accordingly, an object of the present disclosure is to provide a battery that has a current collector plate and a foil exposed part (active material non-covered part) reliably joined.

(6) For solving the above-described problems, the present disclosure provides a secondary battery according to an embodiment including: an electrode wound body that has a positive electrode and a negative electrode stacked with a separator interposed therebetween and has a wound structure; and a positive electrode current-collecting plate and a negative electrode current-collecting plate, accommodated in an exterior can, where the positive electrode includes a first covered part covered with a positive electrode active material layer and a positive electrode active material non-covered part on a positive electrode foil, the negative electrode includes a second covered part covered with a negative electrode active material layer and a negative electrode active material non-covered part on a negative electrode foil, the positive electrode active material non-covered part is joined to the positive electrode current-collecting plate at one end of the electrode wound body, the negative electrode active material non-covered part is joined to the negative electrode current-collecting plate at the other end of the electrode wound body, one or both of the positive electrode active material non-covered part and the negative electrode active material non-covered part have a surface formed by bending toward the central axis of the wound structure and overlapping each other, the surface has grooves, the surface located between the adjacent grooves has a raised part, and at the raised part, at least the positive electrode active material non-covered part is joined to the positive electrode current-collecting plate or the negative electrode active material non-covered part is joined to the negative electrode current-collecting plate.

(7) Further, the present disclosure provides a battery pack including: the secondary battery described above; a controller configured to control the secondary battery; and an exterior body that encloses the secondary battery.

(8) The present disclosure provides an electronic device according to an embodiment including the secondary battery as described herein or the battery pack as described herein.

(9) The present disclosure provides an electric tool according to an embodiment including the battery pack as described herein. The electric tool is configured to use the battery pack as a power

supply.

(10) The present disclosure provides an electric aircraft according to an embodiment including: the battery pack as described herein; a plurality of rotor blades; a motor that rotates each of the rotor blades; a support shaft that supports each of the rotor blades and the motor; a motor controller configured to control rotation of the motor; and a power supply line that supplies power to the motor, where the battery pack is connected to the power supply line.

(11) The present disclosure provides an electric vehicle according to an embodiment including the secondary battery described above, and including a conversion device that receives power supply from the secondary battery to convert the power to a driving force for the electric vehicle, and a controller configured to perform information processing related to vehicle control, based on information on the second battery.

(12) According to at least an embodiment of the present disclosure, the active material non-covered part and the current-collecting plate can be reliably welded, the internal resistance of the battery can be reduced, or a high-power battery can be achieved.

(13) It is to be noted that the contents of the present disclosure are not to be construed as being limited by the effects illustrated in this specification. It should be understood that the effects described in the present specification are only examples, and additional effects may be further provided.

Description

BRIEF DESCRIPTION OF THE FIGURES

(1) FIG. 1 is a sectional view of a battery according to an embodiment of the present disclosure.

(2) FIG. 2 is a diagram illustrating an example of a relationship among a positive electrode, a negative electrode, and a separator disposed in an electrode wound body according to an embodiment of the present disclosure.

(3) FIG. 3A is a plan view of a positive electrode current-collecting plate according to an embodiment of the present disclosure, and FIG. 3B is a plan view of a negative electrode current-collecting plate according to an embodiment of the present disclosure.

(4) FIG. 4A to 4F are diagrams illustrating a process for assembling a battery according to an embodiment of the present disclosure.

(5) FIG. 5 is a diagram for illustrating laser welding and the number of overlapped sheets according to an embodiment of the present disclosure.

(6) FIG. 6A is an enlarged view of a battery according to an embodiment of the present disclosure, and FIG. 6B is a sectional view taken along the AA' cross section of FIG. 6A, and is a view illustrating an example.

(7) FIGS. 7A and 7B are diagrams illustrating Comparative Example 1.

(8) FIGS. 8A and 8B are diagrams illustrating Comparative Example 2.

(9) FIG. 9 is a connection diagram for use in description of a battery pack as an application example according to an embodiment of the present disclosure.

(10) FIG. 10 is a connection diagram for use in description of an electric tool as an application example according to an embodiment of the present disclosure.

(11) FIG. 11 is a connection diagram for use in description of an unmanned aircraft as an application example according to an embodiment of the present disclosure.

(12) FIG. 12 is a connection diagram for use in description of an electric vehicle as an application example according to an embodiment of the present disclosure.

DETAILED DESCRIPTION

(13) As described herein, the present disclosure will be described based on examples with reference to the drawings, but the present disclosure is not to be considered limited to the examples, and

various numerical values and materials in the examples are considered by way of example.

(14) In the embodiment of the present disclosure, a cylindrical lithium ion battery will be described as an example of the secondary battery. Obviously, any battery other than the lithium ion battery or a battery that has any shape other than the cylindrical shape may be used.

(15) First, the overall configuration of the lithium ion battery will be described. FIG. 1 is a schematic sectional view of a lithium ion battery 1. The lithium ion battery 1 is, for example, a cylindrical lithium ion battery 1 that has an electrode wound body 20 is housed inside an exterior can 11 as shown in FIG. 1.

(16) Specifically, the lithium ion battery 1 includes, for example, a pair of insulating plates 12 and 13 and an electrode wound body 20 inside the cylindrical exterior can 11. The lithium ion battery 1 may further, however, include, for example, any one of, or two or more of a positive temperature coefficient (PTC) element, a reinforcing member, and the like inside the exterior can 11.

(17) The exterior can 11 is a member that mainly houses the electrode wound body 20. The exterior can 11 is, for example, a cylindrical container with one end thereof opened and the other end thereof closed. More specifically, the exterior can 11 has an opened end (open end 11N). The exterior can 11 contains, for example, any one of, or two or more of metal materials such as iron, aluminum, and alloys thereof. The surface of the exterior can 11 may be, however, plated with, for example, any one of, or two or more of metal materials such as nickel.

(18) Each of the insulating plates 12 and 13 is, for example, a dish-shaped plate that has a surface perpendicular to the winding axis of the electrode wound body 20, that is, a surface perpendicular to the Z axis in FIG. 1. In addition, the insulating plates 12 and 13 are disposed so as to sandwich the electrode wound body 20 therebetween, for example.

(19) The open end 11N of the exterior can 11 has, for example, a battery cover 14 and a safety valve mechanism 30 are crimped with a gasket 15. The battery cover 14 serves as a “cover member” according to an embodiment of the present disclosure, and the gasket 15 serves as a “sealing member” according to an embodiment of the present disclosure. Thus, with the electrode wound body 20 and the like housed inside the exterior can 11, the exterior can 11 is sealed. Accordingly, the open end 11N of the exterior can 11 has a crimped structure (crimped structure 11R) formed by the battery cover 14 and the safety valve mechanism 30 crimped with the gasket 15. More specifically, a bent part 11P is a so-called crimp part, and the crimped structure 11R is a so-called crimp structure.

(20) The battery cover 14 is a member that closes the open end 11N of the exterior can 11 mainly with the electrode wound body 20 and the like housed inside the exterior can 11. The battery cover 14 contains, for example, the same material as the material that forms the exterior can 11. The central region of the battery cover 14 protrudes in the +Z direction, for example. Thus, the region (peripheral region) of the battery cover 14 other than the central region has contact with, for example, the safety valve mechanism 30.

(21) The gasket 15 is a member mainly interposed between the exterior can 11 (bent part 11P) and the battery cover 14 to seal the gap between the bent part 11P and the battery cover 14. For example, asphalt or the like may be, however, applied to the surface of the gasket 15.

(22) The gasket 15 contains, for example, any one of, or two or more of insulating materials. The types of the insulating materials are not particularly limited, and may be, for example, a polymer material such as a polybutylene terephthalate (PBT) and a polypropylene (PP). In particular, the insulating material is preferably a polybutylene terephthalate. This is because the gap between the bent part 11P and the battery cover 14 is sufficiently sealed while the exterior can 11 and the battery cover 14 are electrically separated from each other.

(23) The safety valve mechanism 30 mainly releases the sealed state of the exterior can 11 to release the pressure (internal pressure) inside the exterior can 11, if necessary, when the internal pressure is increased. The cause of the increase in the internal pressure of exterior can 11 is, for example, a gas generated due to a decomposition reaction of an electrolytic solution during

charging or discharging.

(24) For the cylindrical lithium ion battery, a band-shaped positive electrode **21** and a band-shaped negative electrode **22** are spirally wound with a separator **23** interposed therebetween, impregnated with an electrolytic solution, and housed in the exterior can **11**. The positive electrode **21** is obtained by forming a positive electrode active material layer **21B** on one or both surfaces of a positive electrode foil **21A**, and the material of the positive electrode foil **21A** is, for example, a metal foil made of aluminum or an aluminum alloy. The negative electrode **22** is obtained by forming a negative electrode active material layer **22B** on one or both surfaces of a negative electrode foil **22A**, and the material of the negative electrode foil **22A** is, for example, a metal foil made of nickel, a nickel alloy, copper, or a copper alloy. The separator **23** is a porous and insulating film, which enables transfer of substances such as ions and an electrolytic solution while electrically insulating the positive electrode **21** and the negative electrode **22**.

(25) The positive electrode active material layer **21B** and the negative electrode active material layer **22B** respectively cover most of the positive electrode foil **21A** and the negative electrode foil **22A**, but intentionally, neither of the layers covers one end periphery in the short axis direction of the band. Hereinafter, the part covered with no active material layer **21B** or **22B** is appropriately referred to as an active material non-covered part. In the cylindrical battery, the electrode wound body **20** is wound in such a manner that an active material non-covered part **21C** of the positive electrode and an active material non-covered part **22C** of the negative electrode are overlapped with each other with the separator **23** interposed therebetween so as to face in opposite directions.

(26) FIG. 2 shows an example of a structure with the positive electrode **21**, the negative electrode **22**, and the separator **23** stacked before winding. The active material non-covered part **21C** (the upper hatched part in FIG. 2) of the positive electrode has a width denoted by A, and the active material non-covered part **22C** (the lower hatched part in FIG. 2) of the negative electrode has a width denoted by B. According to one embodiment, $A > B$ is preferred, for example, $A = 7$ (mm) and $B = 4$ (mm). A part of the active material non-covered part **21C** of the positive electrode, protruded from one end of the separator **23** in the width direction, has a length denoted by C, and a part of the active material non-covered part **22C** of the negative electrode, protruded from the other end of the separator **23** in the width direction, has a length denoted by D. According to one embodiment, $C > D$ is preferred, for example, $C = 4.5$ (mm) and $D = 3$ (mm).

(27) The active material non-covered part **21C** of the positive electrode is made of, for example, aluminum, whereas the active material non-covered part **22C** of the negative electrode is made of, for example, copper, and thus, the active material non-covered part **21C** of the positive electrode is typically softer (has a lower Young's modulus) than the active material non-covered part **22C** of the negative electrode. Thus, according to one embodiment, $A > B$ and $C > D$ are more preferred, and in this case, when the active material non-covered part **21C** of the positive electrode and the active material non-covered part **22C** of the negative electrode are bent at the same pressure simultaneously from both electrode sides, the positive electrode **21** and the negative electrode **22** may be similar in the height of the bent part, measured from the tip of the separator **23**. In this case, the active material non-covered parts **21C** and **22C** are bent to appropriately overlap with each other, thus allowing the active material non-covered parts **21C** and **22C** and current-collecting plates **24** and **25** to be easily joined by laser welding. Joining according to one embodiment means joining by laser welding, but the joining method is not limited to laser welding.

(28) For the positive electrode **21**, a section of 3 mm in width, including the boundary between the active material non-covered part **21C** and the active material covered part **21B**, is coated with an insulating layer **101** (gray region part in FIG. 2). Further, the whole region of the active material non-covered part **21C** of the positive electrode, opposed the active material covered part **22B** of the negative electrode with the separator interposed therebetween, is covered with the insulating layer **101**. The insulating layer **101** has the effect of reliably preventing any internal short circuit of the battery **1** if any foreign matter enters between the active material covered part **22B** of the negative

electrode and the active material non-covered part **21C** of the positive electrode. In addition, the insulating layer **101** has the effect of, when an impact is applied to the battery **1**, absorbing the impact and reliably preventing the active material non-covered part **21C** of the positive electrode from being bent or short-circuited with the negative electrode **22**.

(29) The central axis of the electrode wound body **20** has a through hole **26** formed. The through hole **26** is a hole for insertion of a winding core for assembling the electrode wound body **20** and an electrode rod for welding. The electrode wound body **20** is wound in an overlapping manner such that the active material non-covered part **21C** of the positive electrode and the active material non-covered part **22C** of the negative electrode face in the opposite directions, and thus, the active material non-covered part **21C** of the positive electrode is gathered at one (end **41**) of the ends of the electrode wound body **20**, whereas the active material non-covered part **22C** of the negative electrode is gathered at the other (end **42**) of the ends of the electrode wound body **20**. For improving contact with the current-collecting plates **24** and **25** for current extraction, the active material non-covered parts **21C** and **22C** are bent, and the ends **41** and **42** have surfaces formed as flat surfaces. The bending directions are directions from the outer edges **27** and **28** of the ends **41** and **42** toward the through hole **26**, and peripheral active material non-covered parts that are adjacent in the wound state are bent in a manner of overlapping with each other. In this specification, the “flat surface” includes not only a perfectly flat surface but also a surface with some unevenness and surface roughness to the extent that the active material non-covered part and the current collecting plate can be joined.

(30) When each of the active material non-covered parts **21C** and **22C** are bent so as to have an overlap, it seems possible for the surfaces of the ends **41** and **42** to have flat surfaces, but if no processing is performed before bending, wrinkles or voids (voids, spaces) are generated at the ends **41** and **42** at the time of bending, and the surfaces of the ends **41** and **42** have no flat surfaces. In this regard, the “wrinkles” or “voids” are portions where the bent active material non-covered parts **21C** and **22C** are biased, thereby causing the surfaces or the ends **41** and **42** to have no flat surfaces. For preventing the generation of wrinkles and voids, grooves **43** (see, for example, FIG. 4B) are formed in radiation directions from the through hole **26**. The groove **43** extends from the outer edges **27** and **28** of the ends **41** and **42** to the through hole **26** in the central axis. The central axis of the electrode wound body **20** has the through hole **26**, and the through hole **26** is used as a hole into which a welding tool is inserted in the process of assembling the lithium ion battery **1**. The active material non-covered parts **21C** and **22C** have notches at the start of winding the positive electrode **21** and the negative electrode **22** near the through hole **26**. This is for keeping the through hole **26** from being closed in the case of bending toward the through hole **26**. The grooves **43** remain in the flat surfaces also after bending the active material non-covered parts **21C** and **22C**, and parts without the grooves **43** are joined (welded or the like) to the positive electrode current-collecting plate **24** or the negative electrode current-collecting plate **25**. It is to be noted that the grooves **43** as well as the flat surfaces may be joined to a part of the current-collecting plates **24** and **25**.

(31) The detailed configuration of the electrode wound body **20**, that is, the respective detailed configuration of the positive electrode **21**, negative electrode **22**, separator **23**, and electrolytic solution will be described later.

(32) Although the active material non-covered parts **21C** and **22C** are described as being bent at the surfaces of the ends **41** and **42** to form flat surfaces, the flat surfaces are actually not perfectly flat surfaces, and the part between adjacent grooves **43** has a raised part **44** (see FIG. 6B) where the ends **41** and **42** are slightly raised. Accordingly, the success rate of laser welding to the current-collecting plates **24** and **25** varies depending on the positions of the ends **41** and **42**. This will be described in an example.

(33) In a common lithium ion battery, for example, a lead for current extraction is welded to each one of the positive electrode and negative electrode, but this is not suitable for high-rate discharge

because of the high internal resistance of the battery and the temperature increased by heat generation of the lithium ion battery in the case of discharging. Thus, in the lithium ion battery according to one embodiment, the internal resistance of the battery is kept low by disposing the positive electrode current-collecting plate **24** and the negative electrode current-collecting plate **25** at the ends **41** and **42**, and welding at multiple points to the active material non-covered parts **21C** and **22C** of the positive electrode and negative electrode present at the ends **41** and **42**. The ends **41** and **42** are bent to form substantially flat surfaces, which also contributes to the reduction in resistance.

(34) FIG. **3A** and FIG. **3B** show examples of the current-collecting plates. FIG. **3A** shows the positive electrode current-collecting plate **24**, and FIG. **3B** shows the negative electrode current-collecting plate **25**. The material of the positive electrode current-collecting plate **24** is, for example, a metal plate made of a simple substance of aluminum or an aluminum alloy or a composite thereof, and the material of the negative electrode current-collecting plate **25** is, for example, a metal plate made of a simple substance of nickel, a nickel alloy, copper, or a copper alloy or a composite thereof. As shown in FIG. **3A**, the positive electrode current-collecting plate **24** has the shape of a flat fan-shaped part **31** with a rectangular band-shaped part **32** attached thereto. The fan-shaped part **31** has, near the center thereof, a hole **35** formed, and the hole **35** is located at a position corresponding to the through hole **26**.

(35) A hatched part in FIG. **3A** is an insulating part **32A** where an insulating tape is attached to the band-shaped part **32** or an insulating material is applied thereto, and the part below the hatched part in the drawing is a connecting part **32B** to a sealing plate that also serves as an external terminal. It is to be noted that in the case of a battery structure without any metallic center pin (not shown) in the through hole **26**, the band-shaped part **32** has a low probability of coming into contact with a site with a negative electrode potential, and thus, there is no need for the insulating part **32A**. In such a case, the widths of the positive electrode **21** and negative electrode **22** can be increased by an amount corresponding to the thickness of the insulating part **32A** to increase the charge/discharge capacity.

(36) The negative electrode current-collecting plate **25** has substantially the same shape as the positive electrode current-collecting plate **24**, but has a different band-shaped part. The band-shaped part **34** of the negative electrode foil in FIG. **3B** is shorter than the band-shaped part **32** of the positive electrode foil, without any part corresponding to the insulating part **32A**. The band-shaped part **34** has a round protrusion (projection) **37** indicated by a plurality of circles. During resistance welding, current is concentrated on the protrusion, and the protrusion is melted to weld the band-shaped part **34** to the bottom of the exterior can **11**. Similarly to the positive electrode current-collecting plate **24**, the negative electrode current-collecting plate **25** has a hole **36** near the center of a fan-shaped part **33**, and the hole **36** is located at a position corresponding to the through hole **26**. The fan-shaped part **31** of the positive electrode current-collecting plate **24** and the fan-shaped part **33** of the negative electrode current-collecting plate **25** have a fan shape, and thus cover a part of the ends **41** and **42**. The reason that the whole is not covered to allow an electrolytic solution to smoothly permeate the electrode wound body in the assembly of the battery, or to make it easier for the gas generated when the battery reaches an abnormally high-temperature state or overcharge state to be released to the outside of the battery.

(37) The positive electrode active material layer **21B** includes, as a positive electrode active material, any one of, or two or more of positive electrode materials capable of occluding and releasing lithium. However, the positive electrode active material layer **21B** may further include any one of, or two or more of other materials such as a positive electrode binder and a positive electrode conductive agent. The positive electrode material is preferably a lithium-containing compound, and more specifically, is preferably a lithium-containing composite oxide, a lithium-containing phosphate compound, or the like.

(38) The lithium-containing composite oxide is an oxide containing lithium and one, or two or

more other elements (elements other than lithium) as constituent elements, and the oxide has, for example, any of a layered rock salt-type crystal structure, a spinel-type crystal structure, and the like. The lithium-containing phosphate compound is a phosphate compound containing lithium and one, or two or more other elements as constituent elements, and the compound has an olivine-type crystal structure or the like.

(39) The positive electrode binder includes any one of, or two or more of synthetic rubbers and polymer compounds, for example. The synthetic rubbers may be, for example, styrene-butadiene rubbers, fluorine rubbers, ethylene propylene diene, and the like. Examples of the polymer compounds include a polyvinylidene fluoride and a polyimide.

(40) The positive electrode conductive agent includes, for example, any one of, or two or more of carbon materials and the like, for example. The carbon materials may be, for example, graphite, carbon black, acetylene black, Ketjen black, and the like. The positive electrode conductive agent may be, however, a metal material, a conductive polymer, or the like as long as the agent is a conductive material.

(41) The surface of the negative electrode foil **22A** is preferably roughened. This is because the adhesion of the negative electrode active material layer **22B** to the negative electrode foil **22A** is improved due to a so-called anchor effect. In this case, the surface of the negative electrode foil **22A** has only to be roughened at least in a region opposed to the negative electrode active material layer **22B**. The roughening method is, for example, a method such as forming fine particles through the use of electrolytic treatment. The electrolytic treatment provides the surface of the negative electrode foil **22A** with irregularities, because fine particles are formed on the surface of the negative electrode foil **22A** with an electrolytic method in an electrolytic cell. Copper foil prepared by an electrolytic method is generally referred to as electrolytic copper foil.

(42) The negative electrode active material layer **22B** includes, as a negative electrode active material, any one of, or two or more of negative electrode materials capable of occluding and releasing lithium. The negative electrode active material layer **22B** may, however, further include any one of, or two or more of other materials such as a negative electrode binder and a negative electrode conductive agent.

(43) The negative electrode material is, for example, a carbon material. This is because a high energy density can be stably achieved due to the very small change in crystal structure at the time of occlusion and release of lithium. In addition, this is because the carbon materials also function as negative electrode conductive agents, thus improving the conductivity of the negative electrode active material layer **22B**.

(44) The carbon materials may be, for example, graphitizable carbon, non-graphitizable carbon, and graphite. However, the interplanar spacing of the (002) plane in the non-graphitizable carbon is preferably 0.37 nm or more, and the interplanar spacing of the (002) plane in the graphite is preferably 0.34 nm or less. More specifically, the carbon materials may be, for example, pyrolytic carbons, coke, glassy carbon fibers, fired products of organic polymer compounds, activated carbon, and carbon blacks. Examples of the coke include pitch coke, needle coke, and petroleum coke. The fired products of organic polymer compounds are obtained by firing (carbonizing) polymer compounds such as a phenol resin and a furan resin at appropriate temperatures. Besides, the carbon materials may be low-crystallinity carbon subjected to a heat treatment at a temperature of about 1000° C. or lower, or may be amorphous carbon. It is to be noted that the shapes of the carbon materials may be any of fibrous, spherical, granular and scaly.

(45) In the lithium ion battery **1**, when the open-circuit voltage (that is, the battery voltage) in a fully charged case is 4.25 V or higher, the release amount of lithium per unit mass is increased also with the use of the same positive electrode active material as compared with a case where the open-circuit voltage in the fully charged case is 4.20 V, and the amount of the positive electrode active material and the amount of the negative electrode active material are thus adjusted accordingly. Thus, a high energy density is achieved.

(46) The separator **23** is interposed between the positive electrode **21** and the negative electrode **22** to allow passage of lithium ions while preventing a short circuit due to the current caused by the contact between the positive electrode **21** and the negative electrode **22**. The separator **23** is any one of, or two or more of porous membranes such as synthetic resins and ceramics, for example, and may be a laminated film of two or more porous membranes. The synthetic resins may be, for example, polytetrafluoroethylene, polypropylene, polyethylene, and the like.

(47) In particular, the separator **23** may include, for example, the above-mentioned porous film (substrate layer), and a polymer compound layer provided on one or both sides of the substrate layer. This is because the adhesion of the separator **23** to each of the positive electrode **21** and the negative electrode **22** is improved, thus keeping the electrode wound body **20** from warping. Thus, the inhibited decomposition reaction of the electrolytic solution, and also, the suppressed leakage of the electrolytic solution with which the substrate layer impregnated, make the resistance less likely to increase also with repeated charging/discharging, and keep the secondary battery from swelling.

(48) The polymer compound layer contains, for example, a polymer compound such as a polyvinylidene fluoride. This is because the polymer compound is excellent in physical strength and electrochemically stable. The polymer compound may be, however, a compound other than a polyvinylidene fluoride. In the case of forming the polymer compound layer, for example, a solution in which a polymer compound is dissolved in an organic solvent or the like is applied to the substrate layer, and then the substrate layer is dried. It is to be noted that after immersing the substrate layer in the solution, the base material layer may be dried. This polymer compound layer may include any one of, or two or more of insulating particles such as inorganic particles, for example. The type of the inorganic particles is, for example, an aluminum oxide, an aluminum nitride, or the like.

(49) The electrolytic solution includes a solvent and an electrolyte salt. The electrolytic solution may further include, however, any one of, or two or more of other materials such as additives.

(50) The solvent includes any one of, or two or more of nonaqueous solvents such as organic solvents. The electrolytic solution including a nonaqueous solvent is a so-called nonaqueous electrolytic solution.

(51) The nonaqueous solvent is, for example, a cyclic carbonate, a chain carbonate, a lactone, a chain carboxylate, a nitrile (mononitrile), or the like.

(52) The electrolyte salt includes any one of, or two or more of salts such as lithium salts, for example. However, the electrolyte salt may contain a salt other than lithium salts, for example. The salt other than lithium may be, for example, salts of light metals other than lithium.

(53) The lithium salt may be, for example, lithium hexafluorophosphate (LiPF₆), lithium tetrafluoroborate (LiBF₄), lithium perchlorate (LiClO₄), lithium hexafluoroarsenate (LiAsF₆), lithium tetraphenylborate (LiB(C₆H₅)₄), lithium methanesulfonate (LiCH₃SO₃), lithium trifluoromethanesulfonate (LiCF₃SO₃), lithium tetrachloroaluminate (LiAlCl₄), dilithium hexafluorosilicate (Li₂SiF₆), lithium chloride (LiCl) and Lithium bromide (LiBr), and the like.

(54) Above all, any one of, or two or more of lithium hexafluorophosphate, lithium tetrafluoroborate, lithium perchlorate, and lithium hexafluoroarsenate is preferred, and lithium hexafluorophosphate is more preferred.

(55) The content of the electrolyte salt is not particularly limited, but preferably 0.3 mol/kg to 3 mol/kg with respect to the solvent.

(56) A method for manufacturing the lithium ion battery **1** according to one embodiment will be described with reference to FIG. **4A** to FIG. **4F**. First, a positive electrode active material was applied to the surface of the band-shaped positive electrode foil **21A** to form a covered part for the positive electrode **21**, and a negative electrode active material was applied to the surface of the band-shaped negative electrode foil **22A** to form a covered part for the negative electrode **22**. In

this case, the active material non-covered parts **21C** and **22C** without the positive electrode active material or negative electrode active material applied were prepared at one end of the positive electrode **21** in the widthwise direction and one end of the negative electrode **22** in the widthwise direction. Notches were formed in parts of the active material non-covered parts **21C** and **22C**, corresponding to the winding starts at the time of winding. The positive electrode **21** and the negative electrode **22** were subjected to steps such as drying. Then, the electrodes were stacked with the separator **23** interposed therebetween such that the active material non-covered part **21C** of the positive electrode and the active material non-covered part **22C** of the negative electrode were oriented in opposite directions, and spirally wound so as to form the through hole **26** in the central axis and dispose the formed notches near the central axis, thereby preparing the electrode wound body **20** as shown in FIG. 4A.

(57) Next, as shown in FIG. 4B, an end of a thin flat plate (for example, 0.5 mm in thickness) or the like was pressed perpendicularly to the ends **41** and **42** to locally bend the ends **41** and **42** and then prepare the grooves **43**. In accordance with this method, the groove **43** extending toward the central axis was prepared in radiation directions from the through hole **26**. The number of the grooves **43** and the arrangement, shown in FIG. 4B, is considered by way of example only. Then, as shown in FIG. 4C, the same pressure was applied simultaneously from both electrode sides in a direction substantially perpendicular to the ends **41** and **42** to bend the active material non-covered part **21C** of the positive electrode and the active material non-covered part **22C** of the negative electrode, and then form the surfaces of the ends **41** and **42** so as to have substantially flat surfaces. In this case, the pressure was applied such that the active material non-covered parts at the ends **41** and **42** overlapped and then bent toward the through hole **26**. Thereafter, the fan-shaped part **31** of positive electrode current-collecting plate **24** was subjected to laser welding to the end **41**, and the fan-shaped part **33** of the negative electrode current-collecting plate **25** was subjected to laser welding to the end **42**.

(58) Thereafter, as shown in FIG. 4D, the band-shaped parts **32** and **34** of the current-collecting plates **24**, **25** were bent, and the insulating plates **12** and **13** (or insulating tapes) were attached to the positive electrode current-collecting plate **24** and the negative electrode current-collecting plate **25**, the electrode wound body **20** assembled as mentioned above was inserted into the exterior can **11** shown in FIG. 4E, and the bottom of the exterior can **11** was subjected to welding. After injecting an electrolytic solution into the exterior can **11**, sealing was performed with the gasket **15** and the battery cover **14** as shown in FIG. 4F.

EXAMPLES

(59) Hereinafter, the present disclosure will be specifically described with reference to an example based on the lithium ion battery **1** prepared in the manner described above, where the active material non-covered part **21C** and positive electrode current-collecting plate **24** of the positive electrode were laser-welded, whereas the active material non-covered part **22C** and negative electrode current-collecting plate **25** of the negative electrode were laser-welded. It is to be noted that the present disclosure is not to be considered limited to the examples described below.

(60) The number of grooves **43** was 8, the thickness of the positive electrode foil was adjusted to 10 (μm), the thickness of the negative electrode foil was adjusted to 10 (μm), the thickness of the positive electrode current-collecting plate was adjusted to 200 (μm), and the thickness of the negative electrode current-collecting plate was adjusted to 80 (μm). The battery size was 21700. Except for Comparative Example 3, the numbers of overlapped sheets of the active material non-covered parts **21C** and **22C** bent at the end portions **41** and **42** were each 2 or more. The width A of the active material non-covered part **21C** of the positive electrode was adjusted to 7 (mm), the width B of the active material non-covered part **22C** of the negative electrode was adjusted to 4 (mm), the length C of the active material non-covered part **21C** of the positive electrode, protruded from the separator **23**, was adjusted to 4.5 (mm), and the length D of the active material non-covered part **22C** of the negative electrode, protruded from the separator **23**, was subjected to 3

(mm).

(61) FIG. 5 shows a section of a laser-welded part of the positive electrode active material non-covered part **21C** and of the positive electrode current-collecting plate **24**. In the end portion **41**, welding was performed by irradiating laser light **61** in a predetermined range from a point at a distance *a* from the side surface of the electrode wound body. The number *m* of sheets overlapped on the positive electrode side is the number of the active material non-covered parts **21C** (positive electrode foils) welded immediately below the point at the distance *a* in FIG. 5. The point of the distance *a* is a point farthest from the central axis in the trajectory formed by the laser beam **61**. The number of sheets overlapped can be confirmed by cutting the battery along a plane parallel to the central axis and observing the welded part. Omitted is a view of the negative electrode active material non-covered part **22** and negative electrode current-collecting plate **25** laser-welded. The number *m* of sheets overlapped on the negative electrode side is the number of the active material non-covered parts **22C** (negative electrode foils) welded immediately below the point at the distance *a*.

Example

(62) FIG. 6A shows an enlarged view (corresponding to the enlarged view of FIG. 4C) of the end **41** or **42** with eight grooves **43** provided and the active material non-covered parts **21C** and **22C** bent. FIG. 6B shows a sectional view taken along a broken line AA' in FIG. 6A after disposing the current-collecting plate **24** or **25** in an overlapping manner on the end **41** or **42** in FIG. 6A. Laser welding was performed from the side of the current-collecting plate **24** or **25** in the vicinity **51** of the apex of the raised part **44** (region sandwiched by two broken lines in FIG. 6B). As a result, the number of batteries successfully welded was 30 out of 30 batteries.

Comparative Example 1

(63) FIG. 7A shows a sectional view taken along a broken line AA' in FIG. 6A after disposing the current-collecting plate **24** or **25** in an overlapping manner on the end **41** or **42** in FIG. 6A. Laser welding was performed from the side of the current-collecting plate **24** or **25** at a part **52** away from the vicinity **51** of the apex of the raised part **44** (region sandwiched by two broken lines in FIG. 7A). As a result, the welding was failed in some cases. In the case where the welding was failed, as shown in FIG. 7B, a perforation **53** was caused by heat of the laser welding in the current-collecting plate, thereby resulting in burn-through **54** of the current-collecting plate or spattering (not shown). The number of batteries successfully welded was 7 out of 30 batteries.

Comparative Example 2

(64) FIG. 8A shows a sectional view taken along a broken line AA' in FIG. 6A after disposing the current-collecting plate **24** or **25** in an overlapping manner on the end **41** or **42** in FIG. 6A. Laser welding was performed from the side of the current-collecting plate **24** or **25** on a side **55** above the groove (region sandwiched by two broken lines in FIG. 8A). As a result, the welding was failed in most cases. In the case where the welding was failed, as shown in FIG. 8B, a perforation **53** was caused by heat of the laser welding in the current-collecting plate, thereby resulting in burn-through **54** of the current-collecting plate or spattering (not shown). The number of batteries successfully welded was 0 out of 30 batteries.

Comparative Example 3

(65) A battery was prepared under the same conditions as in the above-described example except that the numbers of overlapped sheets of the active material non-covered parts **21C** and **22C** at the ends **41** and **42** were each 1. The current collector plate was perforated or sputtered. The number of batteries successfully welded was 18 out of 30 batteries.

(66) While the embodiment of the present disclosure have been concretely described above, the contents of the present disclosure are not to be considered limited to the embodiment described above, and it is possible to make various modifications based on technical idea of the present disclosure.

(67) Although the number of grooves **43** was 8 in the examples and the comparative examples,

other numbers may be employed. The battery size was 21700, but may be 18650 or any other size. (68) FIG. 9 is a block diagram illustrating a circuit configuration example in the case of applying a battery according to an embodiment of the present disclosure (hereinafter, referred to appropriately as a secondary battery) to a battery pack 300. The battery pack 300 includes an assembled battery 301, an exterior, a switch unit 304 including a charge control switch 302a and a discharge control switch 303a, a current detection resistor 307, a temperature detection element 308, and a control unit (controller) 310.

(69) In addition, the battery pack 300 includes a positive electrode terminal 321 and a negative electrode terminal 322, and in the case of charging, the positive electrode terminal 321 and the negative electrode terminal 322 are connected respectively to a positive electrode terminal and a negative electrode terminal of a charger to perform charging. In addition in the case of using an electronic device, the positive electrode terminal 321 and the negative electrode terminal 322 are connected respectively to a positive electrode terminal and a negative electrode terminal of the electronic device to perform discharging.

(70) The assembled battery 301 has a plurality of secondary batteries 301a connected in series and/or in parallel. The secondary battery 301a is a secondary battery according to the present disclosure. It is to be noted that FIG. 9 shows therein a case where six secondary batteries 301a are connected to arrange two batteries in parallel and three batteries in series (2P3S) as an example, but any other connecting method may be employed, such as u in parallel and v in series (u and v are integers).

(71) The switch unit 304 includes the charge control switch 302a and a diode 302b as well as the discharge control switch 303a and a diode 303b, and the switch unit 304 is controlled by the control unit 310. The diode 302b has a polarity in the reverse direction with respect to the charging current flowing in the direction from the positive electrode terminal 321 to the assembled battery 301 and in the forward direction with respect to the discharging current flowing in the direction from the negative electrode terminal 322 to the assembled battery 301. The diode 303b has a polarity in the forward direction with respect to the charging current and in the reverse direction with respect to the discharging current. It is to be noted that the switch unit 304 is provided on the positive side in the example, but may be provided on the negative side.

(72) The charge control switch 302a is turned off if the battery voltage reaches an overcharge detection voltage, and is controlled by a charge/discharge control unit such that no charging current flows through the current path of the assembled battery 301. After the charge control switch 302a is turned off, only discharging is possible through the diode 302b. In addition, the charge control switch 302a is turned off if a large current flows at the time of charging, and is controlled by the control unit 310 so as to cut off a charging current flowing through the current path of the assembled battery 301. The control unit (controller) 310 includes at least one of a central processing unit (CPU), a processor or the like.

(73) The discharge control switch 303a is turned off if the battery voltage reaches an overdischarge detection voltage, and is controlled by the control unit 310 such that no discharging current flows through the current path of the assembled battery 301. After the discharge control switch 303a is turned off, only charging is possible through the diode 303b. In addition, the discharge control switch 303a is turned off if a large current flows at the time of discharging, and is controlled by the control unit 310 so as to cut off a discharging current flowing through the current path of the assembled battery 301.

(74) The temperature detection element 308 is, for example, a thermistor, is provided in the vicinity of the assembled battery 301 to measure the temperature of the assembled battery 301 and supplies the measured temperature to the control unit 310. The voltage detection unit 311 measures the voltages of the assembled battery 301 and of the secondary batteries 301a constituting the assembled battery, performs A/D conversion of the measured voltages, and supplies the converted voltages to the control unit 310. A current measurement unit 313 measures a current with the use of

the current detection resistor **307**, and supplies the measured current to the control unit **310**.

(75) The switch control unit **314** controls the charge control switch **302a** and discharge control switch **303a** of the switch unit **304**, based on the voltages and current input from the voltage detection unit **311** and the current measurement unit **313**. When the voltage of any of the secondary batteries **301a** becomes equal to or lower than the overcharge detection voltage or the overdischarge detection voltage, or when a large current flows rapidly, the switch control unit **314** transmits a control signal to the switch unit **304** to prevent overcharge, overdischarge, and overcurrent charge.

(76) In this regard, for example, in the case where the secondary battery is a lithium ion secondary battery, the overcharge detection voltage is determined to be, for example, $4.20\text{ V}\pm 0.05\text{ V}$, and the overdischarge detection voltage is determined to be, for example, $2.4\text{ V}\pm 0.1\text{ V}$.

(77) For the charge/discharge switch, for example, a semiconductor switch such as a MOSFET can be used. In this case, the parasitic diode of the MOSFET functions as the diodes **302b** and **303b**. In the case where a P-channel FET is used as the charge/discharge switch, the switch control unit **314** supplies control signals DO and CO respectively to the respective gates of the charge control switch **302a** and discharge control switch **303a**. In the case of the P-channel type, the charge control switch **302a** and the discharge control switch **303a** are turned on by a gate potential that is lower than the source potential by a predetermined value or more. More specifically, in normal charging and discharging operations, the control signals CO and DO are set to a low level to turn on the charge control switch **302a** and the discharge control switch **303a**.

(78) Then, for example, in overcharge or overdischarge, the control signals CO and DO are set to a high level to turn off the charge control switch **302a** and the discharge control switch **303a**.

(79) A memory **317** includes a RAM and a ROM, and includes, for example, an EPROM (Erasable Programmable Read Only Memory) that is a nonvolatile memory. In the memory **317**, the numerical value calculated by the control unit **310**, the internal resistance value of the battery in the initial state for each secondary battery **301a**, measured at the stage of the manufacturing process, and the like are stored in advance, and can be also appropriately rewritten. In addition, the full charge capacity of the secondary battery **301a** is stored therein, thereby allowing, for example, the remaining capacity to be calculated together with the control unit **310**.

(80) A temperature detection unit **318** measures a temperature with the use of the temperature detection element **308**, performs charge/discharge control at the time of abnormal heat generation, and performs a correction in the calculation of the remaining capacity.

(81) The above-described battery according to an embodiment of the present disclosure can be mounted on or used to supply electric power to, for example, electronic devices and electric vehicles, electric aircrafts, and devices such as electric storage devices.

(82) Examples of the electronic devices include lap-top computers, smartphones, tablet terminals, PDAs (personal digital assistants), mobile phones, wearable terminals, cordless phone handsets, video movies, digital still cameras, electronic books, electronic dictionaries, music players, radios, headphones, game machines, navigation systems, memory cards, pacemakers, hearing aids, electric tools, electric shavers, refrigerators, air conditioners, televisions, stereos, water heaters, microwave ovens, dishwashers, washing machines, dryers, lighting devices, toys, medical devices, robots, road conditioners, and traffic lights.

(83) Furthermore, examples of the electric vehicles include railway vehicles, golf carts, electric carts, and electric automobiles (including hybrid automobiles), and the battery is used as a driving power supply or an auxiliary power supply for the electric vehicles. Examples of the electric storage devices include power supplies for power storage for buildings such as houses or power generation facilities.

(84) Among the above-described application examples, a specific example of an electric storage system in which an electric storage device with the above-described battery according to the present disclosure applied is used will be described below.

(85) An example of an electric tool, for example, an electric driver to which the present disclosure can be applied will be schematically described with reference to FIG. 10. The electric driver **431** has a motor **433** such as a DC motor housed in a main body. The rotation of the motor **433** is transmitted to a shaft **434**, and the shaft **434** drives a screw into a target object. The electric driver **431** is provided with a trigger switch **432** operated by a user.

(86) A battery pack **430** and a motor control unit (motor controller) **435** are housed in a lower housing of a handle of the electric driver **431**. As the battery pack **430**, the battery pack **300** can be used. The motor control unit (motor controller) **435** controls the motor **433**. Each unit of the electric driver **431** other than the motor **433** may be controlled by the motor control unit **435**. Although not shown, the battery pack **430** and the electric driver **431** are engaged by engagement members provided respectively. As described later, each of the battery pack **430** and the motor control unit (motor controller) **435** includes at least one of a microcomputer, a central processing unit (CPU), a processor or the like. Battery power is supplied from the battery pack **430** to the motor control unit **435**, and information on the battery pack **430** is communicated between the microcomputers.

(87) The battery pack **430** is, for example, detachable from the electric driver **431**. The battery pack **430** may be built in the electric driver **431**. The battery pack **430** is attached to a charging device at the time of charging. It is to be noted that when the battery pack **430** is attached to the electric driver **431**, a part of the battery pack **430** may be exposed to the outside of the electric driver **431** to allow the user to visibly recognize the exposed part. For example, the exposed part of the battery pack **430** may be provided with an LED to allow the user to check light emission and non-light emission of the LED.

(88) The motor control unit **435** controls, for example, the rotation/stop and rotation direction of the motor **433**. Furthermore, power supply to the load is cut off at the time of overdischarge. For example, the trigger switch **432** is inserted between the motor **433** and the motor control unit **435**, and when the user pushes the trigger switch **432**, power is supplied to the motor **433** to rotate the motor **433**. When the user returns the trigger switch **432**, the rotation of the motor **433** is stopped.

(89) An example in which the present disclosure is applied to a power supply for an electric aircraft will be described with reference to FIG. 11. The present disclosure can be applied to a power supply of an unmanned aircraft (so-called drone). FIG. 11 is a plan view of an unmanned aircraft. The airframe includes a cylindrical or rectangular tube body as a central part, and support shafts **442a** to **442f** fixed to an upper part of the body. As an example, the body has a hexagonal tubular shape, and the six support shafts **442a** to **442f** are adapted to extend radially in an equiangular manner from the center of the body. The body and the support shafts **442a** to **442f** are made of a lightweight and high-strength material.

(90) Motors **443a** to **443f** as driving sources for rotor blades are attached respectively to tips of the support shafts **442a** to **442f**. Rotor blades **444a** to **444f** are attached to the rotation shafts of the motors **443a** to **443f**. A circuit unit **445** including a motor control circuit (motor controller) for controlling each motor is attached to the central part (the upper part of the body portion) where the support shafts **442a** to **442f** intersect. The motor control circuit (motor controller) includes at least one of a central processing unit (CPU), a processor or the like.

(91) Furthermore, a battery unit as a power source is disposed at a position below the body. The battery unit includes three battery packs so as to supply electric power the pair of a motor and a rotor blade that have an opposing interval of 180 degrees. Each battery pack includes, for example, a lithium ion secondary battery and a battery control circuit that controls charging and discharging. The battery pack **300** can be used as the battery pack. The motor **443a** and the rotor blade **444a** form a pair with the motor **443d** and the rotor blade **444d**. Similarly, (motor **443b** and rotor blade **444b**) form a pair with (motor **443e** and rotor blade **444e**), and (motor **443c** and rotor blade **444c**) form a pair with (motor **443f** and rotor blade **444f**). These pairs are equal in number to the battery packs.

(92) An example of applying the present disclosure to an electric storage system for an electric vehicle will be described with reference to FIG. 12. FIG. 12 schematically illustrates an example of the configuration of a hybrid vehicle that adopts a series hybrid system to which the present disclosure is applied. The series hybrid system is intended for a vehicle that runs on an electric power-driving force conversion device, with the use of electric power generated by a generator driven by an engine, or the electric power stored once in the battery.

(93) The hybrid vehicle **600** carries an engine **601**, a generator **602**, the electric power-driving force conversion device **603**, a driving wheel **604a**, a driving wheel **604b**, a wheel **605a**, a wheel **605b**, a battery **608**, a vehicle control device **609**, various sensors **610**, and a charging port **611**. The above-described battery pack **300** according to the present disclosure is applied to the battery **608**.

(94) The hybrid vehicle **600** travels with the electric power-driving force conversion device (converter) **603** as a power source. An example of the electric power-driving force conversion device **603** is a motor. The electric power-driving force conversion device **603** is operated by the electric power of the battery **608**, and the torque of the electric power-driving force conversion device **603** is transmitted to the driving wheels **604a** and **604b**. It is to be noted that the electric power-driving force conversion device **603** can be applied to both an alternate-current motor and a direct-current motor by using direct current-alternate current (DC-AC) or reverse conversion (AC-DC conversion) in a required location. The various sensors **610** control the engine rotation speed via the vehicle control device (vehicle controller) **609**, and control the position (throttle position) of a throttle valve, not shown. The various sensors **610** include a speed sensor, an acceleration sensor, an engine rotation speed sensor, and the like. The vehicle control device (vehicle controller) **609** includes at least one of a central processing unit (CPU), a processor or the like.

(95) The torque of the engine **601** is transmitted to the generator **602**, and the torque makes it possible to reserve, in the battery **608**, the electric power generated by the generator **602**.

(96) When the hybrid vehicle **600** is decelerated by a braking mechanism, not shown, the resistance force during the deceleration is applied as torque to the electric power-driving force conversion device **603**, and the regenerative electric power generated by the electric power-driving force conversion device **603** is reserved in the battery **608** by the torque.

(97) The battery **608** is connected to a power source outside the hybrid vehicle **600**, thereby making it also possible to receive electric power supply from the external power supply with the charging port **611** as an input port, and then reserve the received power.

(98) Although not shown, the vehicle may be provided with an information processing device that performs information processing related to vehicle control, based on information on the secondary battery. Examples of such an information processing device include, for example, an information processing device that displays the remaining battery level, based on information on the remaining level of the battery.

(99) It is to be noted that as an example, the series hybrid vehicle has been described above, which runs on the motor with the use of the electric power generated by the generator driven by the engine, or the electric power stored once in the battery. However, the present disclosure can be also effectively applied to parallel hybrid vehicles which use the outputs of both an engine and a motor as a driving source, and appropriately switch three systems of running on only the engine, running on only the motor, and running on the engine and the motor. Furthermore, the present disclosure can be also effectively applied to so-called electric vehicles that run on driving by only a driving motor without using any engine.

(100) It should be understood that various changes and modifications to the presently preferred embodiments described herein will be apparent to those skilled in the art. Such changes and modifications can be made without departing from the spirit and scope of the present subject matter and without diminishing its intended advantages. It is therefore intended that such changes and modifications be covered by the appended claims.

Claims

1. A secondary battery comprising: an electrode wound body that has a positive electrode and a negative electrode stacked with a separator interposed therebetween and has a wound structure; and a positive electrode current-collecting plate and a negative electrode current-collecting plate, wherein the electrode wound body, the positive electrode current-collecting plate and the negative electrode current-collecting plate are accommodated in an exterior can, wherein the positive electrode includes a first covered part covered with a positive electrode active material layer and a positive electrode active material non-covered part on a positive electrode foil, the negative electrode comprises a second covered part covered with a negative electrode active material layer and a negative electrode active material non-covered part on a negative electrode foil, the positive electrode active material non-covered part is joined to the positive electrode current-collecting plate at one end of the electrode wound body, the negative electrode active material non-covered part is joined to the negative electrode current-collecting plate at the other end of the electrode wound body, one or both of the positive electrode active material non-covered part and the negative electrode active material non-covered part have a surface formed by bending toward a central axis of the wound structure and overlapping each other, the surface has grooves, the surface located between the adjacent grooves includes a raised part raising outward, and at the raised part, at least the positive electrode active material non-covered part is joined to the positive electrode current-collecting plate or the negative electrode active material non-covered part is joined to the negative electrode current-collecting plate.
2. The secondary battery according to claim 1, wherein a number of overlapped sheets of the positive electrode foil in the positive electrode active material non-covered part, or a number of overlapped sheets of the negative electrode foil in the negative electrode active material non-covered part is 2 or more.
3. The secondary battery according to claim 1, wherein a material of the positive electrode current-collecting plate includes aluminum or an aluminum alloy.
4. The secondary battery according to claim 2, wherein a material of the positive electrode current-collecting plate includes aluminum or an aluminum alloy.
5. The secondary battery according to claim 1, wherein a material of the negative electrode current-collecting plate includes a simple substance of nickel, a nickel alloy, copper, a copper alloy, or a composite thereof.
6. The secondary battery according to claim 1, wherein a width of the positive electrode active material non-covered part is larger than a width of the negative electrode active material non-covered part, an end of the positive electrode active material non-covered part and an end of the negative electrode active material non-covered part is protruded outward from the separator, and a length of a part of the positive electrode active material non-covered part protruded from one end of the separator in a width direction is larger than a length of a part of the negative electrode active material non-covered part protruded from the other end of the separator in the width direction.
7. The secondary battery according to claim 1, wherein a part of the positive electrode active material non-covered part that faces the negative electrode with the separator interposed therebetween has an insulating layer.
8. A battery pack comprising: the secondary battery according to claim 1; a controller configured to control the secondary battery; and an exterior body that encloses the secondary battery.
9. An electronic device comprising the secondary battery according to claim 1.
10. An electronic device comprising the secondary battery according to the battery pack according to claim 8.
11. An electric tool comprising the battery pack according to claim 8, wherein the electric tool is configured to use the battery pack as a power supply.

12. An electric aircraft comprising: the battery pack according to claim 8; a plurality of rotor blades; a motor that rotates each of the rotor blades; a support shaft that supports each of the rotor blades and the motor; a motor controller configured to control rotation of the motor; and a power supply line that supplies power to the motor, wherein the battery pack is connected to the power supply line.
13. The electric aircraft according to claim 12, comprising: a plurality of pairs of the rotor blades facing each other; and a plurality of the battery packs, wherein the plurality of pairs of rotor blades and the plurality of battery packs are equal in number.
14. An electric vehicle including the secondary battery according to claim 1, comprising: a conversion device that receives power supply from the secondary battery to convert the power to a driving force for the electric vehicle; and a controller configured to perform information processing related to vehicle control, based on information on the secondary battery.
15. The secondary battery according to claim 1, wherein in the vicinity of the apex of the raised part, the positive electrode active material non-covered part is joined to the positive electrode current-collecting plate and/or the negative electrode active material non-covered part is joined to the negative electrode current-collecting plate.
-