

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250279262

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

LIM; Hanjin et al.

BATCH-TYPE APPARATUS FOR ATOMIC LAYER ETCHING (ALE), AND ALE METHOD AND SEMICONDUCTOR DEVICE MANUFACTURING METHOD BASED ON THE SAME APPARATUS

Abstract

A batch-type apparatus for atomic layer etching (ALE), which is capable of ALE-processing several wafers at the same time, and an ALE method and a semiconductor device manufacturing method based on the batch-type apparatus, are provided. The ALE method including: performing, by a batch-type apparatus for ALE, a fluorination process of an ALE process by injecting a first source gas; and performing, by the batch-type apparatus for ALE, a ligand exchange process of the ALE process by injecting a second source gas, wherein the batch-type apparatus for ALE includes a wafer stacking container that has therein a plurality of wafers that are arranged in a vertical direction, and the batch-type apparatus for ALE further includes one or more process chambers.

Inventors: LIM; Hanjin (Seoul, KR), KIM; Younsoo (Yongin-si, KR), MOON; Sunmin (Yongin-si, KR), PARK; Jungmin (Seoul, KR), JUNG; Hyungsuk (Suwon-si, KR)

Applicant: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)

Family ID: 85288628

Appl. No.: 19/211571

Filed: May 19, 2025

Foreign Application Priority Data

KR

10-2021-0111874

Aug. 24, 2021

Related U.S. Application Data

parent US division 17683506 20220301 parent-grant-document US 12334308 child US 19211571

Publication Classification

Int. Cl.: H01J37/32 (20060101); H01L21/67 (20060101)

U.S. Cl.:

CPC H01J37/3244 (20130101); H01J37/32357 (20130101); H01J37/32522 (20130101); H01J37/32715 (20130101); H01J37/32834 (20130101); H01J37/32899 (20130101); H01L21/67069 (20130101); H01J2237/201 (20130101); H01J2237/334 (20130101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This application is a Divisional application of U.S. application Ser. No. 17/683,506, filed on Mar. 1, 2022, which is based on and claims priority under 35 U.S.C. § 119 to Korean Patent Application No. 10-2021-0111874, filed on Aug. 24, 2021, in the Korean Intellectual Property Office, the disclosures of which are incorporated by reference herein in their entireties.

BACKGROUND

[0002] Embodiments of the present disclosure relate to an atomic layer etching (ALE) apparatus and method, and more particularly, to an ALE apparatus and method in which an ALE process may be performed simultaneously on a plurality of wafers.

[0003] As the geometries of structures on semiconductor substrates continue to decrease and types of structures evolve, etching challenges are increasing. One of the techniques used to solve this problem is ALE. Herein, ALE may refer to a technique that typically etches material layers with atomic precision. For example, ALE may remove one or several mono-molecular layers at a time. In general, the ALE process may proceed by chemically modifying a surface to be etched and then selectively removing the modified layer.

SUMMARY

[0004] Embodiments of the present disclosure provide a batch-type apparatus for atomic layer etching (ALE), which is capable of simultaneously ALE-processing several wafers, and an ALE method and a semiconductor device manufacturing method based on the batch-type apparatus.

[0005] A problem to be solved by embodiments of the present disclosure may not be limited to the foregoing, and other problems would be apparent to one of ordinary skill in the art from the following description.

[0006] According to one or more embodiments, a batch-type apparatus for atomic layer etching (ALE) is provided. The batch-type apparatus includes: a wafer stacking container that is configured to have therein a plurality of wafers that are arranged in a vertical direction, and the batch-type apparatus further including at least one process chamber. Each of the at least one process chamber including: an inner tube that extends in the vertical direction, and configured to include the wafer stacking container therein; a plurality of nozzles arranged in a first outer portion in the inner tube in a horizontal direction, the plurality of nozzles extending in the vertical direction and configured to supply a gas to the plurality of wafers; and a heater that surrounds the inner tube and is configured to adjust a temperature in the inner tube, wherein each of the plurality of nozzles includes a plurality of gas injection holes, the plurality of gas injection holes provided at heights corresponding to heights of the plurality of wafers, respectively, and wherein the inner tube includes a gas outlet in a second outer portion in the inner tube, opposite to the first outer portion in the horizontal direction.

[0007] According to one or more embodiments, a batch-type apparatus for atomic layer etching

(ALE) is provided. The batch-type apparatus for ALE includes: a first process chamber of a batch type; a second process chamber of a batch type, arranged adjacent to the first process chamber; a gas supply configured to supply a gas to the first process chamber and the second process chamber; and a gas exhaust configured to discharge the gas from the first process chamber and the second process chamber. Each of the first process chamber and the second process chamber includes: a wafer stacking container that is configured to have therein a plurality of wafers that are arranged in a vertical direction, an inner tube that extends in the vertical direction, the wafer stacking container inside the inner tube, a plurality of nozzles arranged in a first outer portion in the inner tube in a horizontal direction, the plurality of nozzles extending in the vertical direction and configured to supply the gas to the plurality of wafers, and a heater that surrounds the inner tube and is configured to adjust a temperature of the inner tube, wherein each of the plurality of nozzles includes a plurality of gas injection holes, the plurality of gas injection holes provided at heights corresponding to heights of the plurality of wafers, respectively, and wherein the inner tube includes a gas outlet in a second outer portion in the inner tube, opposite to the first outer portion in the horizontal direction.

[0008] An atomic layer etching (ALE) method is provided. The ALE method includes: performing, by a batch-type apparatus for ALE, a fluorination process of an ALE process by injecting a first source gas; and performing, by the batch-type apparatus for ALE, a ligand exchange process of the ALE process by injecting a second source gas. The batch-type apparatus for ALE includes a wafer stacking container that has therein a plurality of wafers that are arranged in a vertical direction, and the batch-type apparatus for ALE further includes one or more process chambers. Each of the one or more process chambers includes: an inner tube that extends in the vertical direction, the inner tube configured to receive the wafer stacking container therein, a plurality of nozzles arranged in a first outer portion in the inner tube in a horizontal direction, the plurality of nozzles extending in the vertical direction and configured to supply a gas to the plurality of wafers, and a heater that surrounds the inner tube and is configured to adjust a temperature of the inner tube, wherein the performing of the fluorination process includes supplying the first source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers, and the performing of the ligand exchange process includes supplying the second source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers.

[0009] According to one or more embodiments, a semiconductor device manufacturing method is provided. The semiconductor device manufacturing method includes: forming a dielectric film on a semiconductor substrate; crystallizing the dielectric film through heat treatment; performing an atomic layer etching (ALE) process on the dielectric film; determining whether a thickness of the dielectric film is less than or equal to a set target thickness; and performing a subsequent process on the semiconductor substrate based on determining that the thickness of the dielectric film is less than or equal to the set target thickness. The performing of the ALE process on the dielectric film includes: performing, by a batch-type apparatus for ALE, a fluorination process of the ALE process by injecting a first source gas; supplying a first purge gas; performing, by the batch-type apparatus for ALE, a ligand exchange process of the ALE process by injecting a second source gas; and supplying a second purge gas. The batch-type apparatus for ALE includes a wafer stacking container that has therein a plurality of wafers that are arranged in a vertical direction, and the batch-type apparatus for ALE further includes one or more process chambers. Each of the one or more process chambers includes: an inner tube that extends in the vertical direction, the wafer stacking container configured to be inserted inside the inner tube, a plurality of nozzles arranged in a first outer portion in the inner tube in a horizontal direction, the plurality of nozzles extending in the vertical direction, and configured to supply a gas to the plurality of wafers, and a heater that surrounds the inner tube and is configured to adjust a temperature of the inner tube, wherein the performing of the fluorination process includes supplying the first source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers, and

wherein the performing of the ligand exchange process includes supplying the second source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] Embodiments of the present disclosure will be more clearly understood from the following detailed description taken in conjunction with the accompanying drawings in which:

[0011] FIG. 1 is a block diagram of a batch-type apparatus for atomic layer etching (ALE), according to an embodiment of the present disclosure;

[0012] FIG. 2A is a vertical cross-sectional view of a process chamber in the batch-type apparatus for ALE of FIG. 1;

[0013] FIG. 2B is a horizontal cross-sectional view of the process chamber in the batch-type apparatus for ALE of FIG. 1;

[0014] FIG. 2C is a perspective view of the process chamber in the batch-type apparatus for ALE of FIG. 1;

[0015] FIG. 3A is a conceptual view showing a procedure of an ALE process in the batch-type apparatus for ALE of FIG. 1;

[0016] FIG. 3B is a conceptual view showing a procedure of an ALE process in the batch-type apparatus for ALE of FIG. 1;

[0017] FIG. 4A is a perspective view showing in more detail a shape of a nozzle in the batch-type apparatus for ALE of FIG. 1;

[0018] FIG. 4B is a perspective view showing in more detail a shape of a nozzle in the batch-type apparatus for ALE of FIG. 1;

[0019] FIG. 4C is a perspective view showing in more detail a shape of a nozzle in the batch-type apparatus for ALE of FIG. 1;

[0020] FIG. 5A is a vertical cross-sectional view showing in more detail a shape of a gas outlet formed in an inner tube, in the batch-type apparatus for ALE of FIG. 1;

[0021] FIG. 5B is a vertical cross-sectional view showing in more detail a shape of a gas outlet formed in an inner tube, in the batch-type apparatus for ALE of FIG. 1;

[0022] FIG. 5C is a vertical cross-sectional view showing in more detail a shape of a gas outlet formed in an inner tube, in the batch-type apparatus for ALE of FIG. 1;

[0023] FIG. 6A is a perspective view of a wafer stacking container, in the batch-type apparatus for ALE of FIG. 1;

[0024] FIG. 6B is a plane view of the wafer stacking container, in the batch-type apparatus for ALE of FIG. 1;

[0025] FIG. 6C is a perspective view of the wafer stacking container, in the batch-type apparatus for ALE of FIG. 1;

[0026] FIG. 7A is a block diagram of a gas supply apparatus, in the batch-type apparatus for ALE of FIG. 1;

[0027] FIG. 7B is a block diagram of a gas supply apparatus, in the batch-type apparatus for ALE of FIG. 1;

[0028] FIG. 7C is a block diagram of a gas supply apparatus, in the batch-type apparatus for ALE of FIG. 1;

[0029] FIG. 8 is a block diagram of a gas exhaust apparatus, in the batch-type apparatus for ALE of FIG. 1;

[0030] FIG. 9A is a block diagram of a batch-type apparatus for ALE, according to an embodiment of the present disclosure;

[0031] FIG. **9B** is a block diagram of a batch-type apparatus for ALE, according to an embodiment of the present disclosure;

[0032] FIG. **9C** is a conceptual view of a batch-type apparatus for ALE, according to an embodiment of the present disclosure;

[0033] FIG. **10A** is a flow chart schematically showing an ALE method based on a batch-type apparatus for ALE, according to embodiments of the present disclosure;

[0034] FIG. **10B** is a flow chart schematically showing an ALE method based on a batch-type apparatus for ALE, according to embodiments of the present disclosure;

[0035] FIG. **11** is a flowchart schematically showing a semiconductor device manufacturing method based on a batch-type apparatus for ALE, according to embodiments of the present disclosure.

DETAILED DESCRIPTION

[0036] Hereinafter, embodiments of the present disclosure will be described in detail with reference to the accompanying drawings. Like components in the drawings will be referred to as like reference numerals, and may not be repeatedly described.

[0037] FIG. **1** is a block diagram of a batch-type apparatus for atomic layer etching (ALE), according to an embodiment of the present disclosure, and FIGS. **2A** through **2C** are respectively a vertical cross-sectional view, a horizontal cross-sectional view, and a perspective view of a process chamber in the batch-type apparatus for ALE of FIG. **1**. FIG. **2C** shows a wafer stacking container **101**, a process tube **110**, and a nozzle **120**, omitting a heater and a chamber cover.

[0038] Referring to FIGS. **1** through **2C**, a batch-type apparatus **1000** for ALE according to an embodiment may include a batch-type process chamber (hereinafter, simply referred to as a 'process chamber') **100**, a gas supply apparatus **200** (also referred to as a 'gas supply'), and a gas exhaust apparatus **300** (also referred to as a 'gas exhaust').

[0039] The process chamber **100** may be a device capable of simultaneously performing an ALE process on a plurality of the wafer **500**. The process chamber **100** may include the wafer stacking container **101**, the process tube **110**, the nozzle **120**, a heater **130**, and a chamber cover **140**.

[0040] The wafer stacking container **101** may be a device that vertically stacks a wafer that is a target of an ALE process. For example, as illustrated in FIG. **2C**, several tens of or several hundreds of the wafer **500** may be arranged at certain intervals in a vertical direction in the wafer stacking container **101**. A structure of the wafer stacking container **101** is described in more detail with reference to FIGS. **6A** through **6C**.

[0041] The process tube **110** may be a vertical process tube having a cylindrical tube shape extending in the vertical direction. In the batch-type apparatus **1000** for ALE according to the current embodiment, the process tube **110** may include an inner tube **112** and an outer tube **114**. The inner tube **112** may have the shape of a cylindrical tube extending in the vertical direction, and may have a closed top. The inner tube **112** may include a heat-resistant material, for example, quartz (SiO₂), silicon carbide (SiC), etc. However, a material of the inner tube **112** is not limited to the above-described materials. A processing space may be formed inside the inner tube **112**. As a result, as shown in FIG. **2A** or **2C**, the wafer stacking container **101** may be inserted into the processing space of the inner tube **112**. Although not shown, the process tube **110** may include a waiting room in a bottom portion of the inner tube **112**, and the wafer stacking container **101** may be introduced into the waiting room from the outside of the process tube **110** before the ALE process and may be moved to the inner tube **112** to be arranged in the processing space of the inner tube **112**.

[0042] The outer tube **114** may have a shape surrounding the inner tube **112**. For example, the outer tube **114** may also have the shape of a cylindrical tube extending in the vertical direction, and may have a closed top. The outer tube **114** may include a heat-resistant material, for example, SiO₂, SiC, etc. However, a material of the outer tube **114** is not limited to the above-described materials. When process gases are injected into the inner tube **112** through the nozzle **120**, and an exhaust gas

is discharged through a gas outlet **116** of the inner tube **112**, the exhaust gas may be discharged through a space between the inner tube **112** and the outer tube **114**. Depending on an embodiment, the outer tube **114** may be omitted. For example, the process tube **110** may include the inner tube **112** without an outer tube, and the heater **130** and the chamber cover **140** may directly surround the inner tube **112**.

[0043] The nozzle **120** may be a device that supplies a process gas to the wafer **500**. Herein, the process gas may be a concept including a source gas, an atmospheric gas, a purge gas, etc. The process gas is described in more detail with reference to FIGS. 3A and 3B.

[0044] The nozzle **120** may be arranged in a first outer portion Op1 inside the inner tube **112**. Herein, the first outer portion Op1 may be a relative concept with respect to a second outer portion Op2 that is adjacent to a portion of the inner tube **112** in which the gas outlet **116** is formed. Referring to FIG. 2B, a portion where the nozzle **120** is arranged may correspond to the first outer portion Op1 inside the inner tube **112**, and a portion opposite to the first outer portion Op1 in a horizontal direction may correspond to the second outer portion Op2 inside the inner tube **112**. As described above, the gas outlet **116** may be formed in a portion of the inner tube **112**, at the second outer portion Op2.

[0045] The nozzle **120** may have a pipe column shape extending in the vertical direction. In addition, a plurality of gas injection holes (see gas injection hole **122** of FIG. 4A) may be formed in a side of the nozzle **120**. The process gas may be injected into the inner tube **112** through a gas injection hole **122** and thus supplied onto the wafer **500**. The shape of the nozzle **120** and the gas injection hole **122** is described in more detail with reference to FIGS. 4A to 4C.

[0046] The nozzle **120** may be arranged in plural inside the inner tube **112**. For example, at least three nozzles **120** may be arranged inside the inner tube **112**. More specifically, in the ALE process, the nozzle **120** may be divided into four types of nozzles according to functions. For example, the nozzle **120** may include a first source gas nozzle for supplying a first source gas for a fluorination process, a second source gas nozzle for supplying a second source gas for a ligand exchange process, an atmospheric gas nozzle for supplying an atmosphere gas, and a purge gas nozzle for supplying a purge gas. The fluorination process and the ligand exchange process are described in more detail with reference to FIGS. 3A and 3B.

[0047] In the batch-type apparatus **1000** for ALE according to the current embodiment, a plurality of nozzles **120** may be arranged inside the inner tube **112**, and the plurality of nozzles **120** may include all of four types of nozzles. According to an embodiment, the plurality of nozzles **120** may include three types of nozzle. For example, the plurality of nozzles **120** may include the first source gas nozzle, the atmosphere gas nozzle, and the purge gas nozzle, or may include the second source gas nozzle, the atmosphere gas nozzle, and the purge gas nozzle. Moreover, according to an embodiment, the plurality of nozzles **120** may include three or four types of nozzle, but may include at least one type of nozzle in plural. For example, when the plurality of nozzles **120** include all of four types of nozzle, the first source gas nozzle and the second source gas nozzle may be included in plural, respectively. In addition, when the plurality of nozzles **120** include three types of nozzle, the first source gas nozzle or the second source gas nozzle may be included in plural.

[0048] The heater **130** may have a shape surrounding the process tube **110**. Thus, the heater **130** may have a cylindrical tube shape similar to the process tube **110**. The heater **130** may heat the inside of the inner tube **112** and the wafer **500** to an appropriate temperature. In other words, the heater **130** may heat the inside of the inner tube **112** and the wafer **500** to maintain the inside of the inner tube **112** at an appropriate temperature, thereby smoothly performing the ALE process.

[0049] The chamber cover **140** may cover an upper portion of the process chamber **100**. According to an embodiment, a heater may be arranged inside the chamber cover **140**. The chamber cover **140** may heat the upper space inside the inner tube **112** through the heater.

[0050] The gas supply apparatus **200** may be an apparatus that supplies a process gas to the process chamber **100**. The process gas may be supplied from the gas supply apparatus **200** to the inside of

the inner tube **112** through a supply pipe **162** and the nozzle **120**. The gas supply apparatus **200** is described in more detail with reference to FIGS. 7A through 7C.

[0051] The gas exhaust apparatus **300** may be an apparatus that discharges the exhaust gas remaining in the process chamber **100** after a process. For example, the exhaust gas from the inner tube **112** may be delivered to the gas exhaust apparatus **300** through a passage between the inner tube **112** and the outer tube **114**, and the exhaust pipe **164**, and may be discharged to the outside through the gas exhaust apparatus **300**. The gas exhaust apparatus **300** is described in more detail with reference to FIG. 8.

[0052] The batch-type apparatus **1000** for ALE according to the current embodiment may include the process chamber **100** having the process tube **110**, which is vertical. Thus, the batch-type apparatus **1000** for ALE may simultaneously perform the ALE process on the plurality of the wafer **500**. For example, the batch-type apparatus **1000** for ALE according to the current embodiment may simultaneously perform the ALE process on 25 through 100 wafers. For reference, a large number of wafers more than or equal to 50 wafers may be arranged at narrow intervals in the wafer stacking container **101** or a small number of wafers less than 50 wafers may be arranged at wide intervals in the wafer stacking container **101**. When a large number of wafers are arranged within the wafer stacking container **101**, a large number of wafers may be processed at a time, thereby increasing a processing speed of wafers. When a small number of wafers are arranged inside the wafer stacking container **101**, an interval between wafers may increase and a flow of process gases may be smooth to achieve a uniform process, thereby improving reliability. Thus, according to a type of an ALE process, the number of the wafer **500** arranged inside the wafer stacking container **101** may be properly adjusted, thus optimizing processing speed and reliability.

[0053] In addition, with reference to FIGS. 9A to 9C, a batch-type apparatus **1000a** and a batch-type apparatus **1000b** for ALE according to embodiments may include two process chambers, for example, a first process chamber **100-1** and a second process chamber **100-2**, having a dual tube structure. Consequently, the batch-type apparatus **1000a** and the batch-type apparatus **1000b** for ALE according to embodiments may perform an ALE process in each of the two process chambers, that is, the first process chamber **100-1** and the second process chamber **100-2**, when a process temperature for each operation of the ALE process is identical. In addition, when the process temperature for each operation of the ALE process is different, the ALE process may be performed by performing a pre-process in the first process chamber **100-1** and performing a post-process in the second process chamber **100-2**. Thus, the batch-type apparatus **1000a** and the batch-type apparatus **1000b** for ALE according to embodiments may efficiently perform the ALE process on the plurality of the wafer **500** in correspondence to the process temperature for each operation of the ALE process.

[0054] FIGS. 3A and 3B are conceptual views showing a procedure of an ALE process in the batch-type apparatus for ALE of FIG. 1. A description will be made with reference to FIGS. 1 through 2C together. In the batch-type apparatus for ALE according to embodiments, the ALE process proceeds through two operations, in which FIG. 3A shows a first operation of the two operations and FIG. 3B shows a second operation of the two operations.

[0055] Referring to FIG. 3A, first, in the first operation of the ALE process, a fluorination process may be performed by supplying a fluorine gas and adsorbing the fluorine gas to a crystalline metal oxide thin film. In FIG. 3A, HF is an example of the fluorine gas of the fluorination process, the fluorine gas is not limited to HF. For example, the fluorine gas may include SF₄, XeF₄, etc. In addition, although an aluminum oxide (Al₂O₃) thin film is an example of a target thin film of the ALE process, the target thin film of the ALE process is not limited thereto. For example, the target thin film of the ALE process may include a metal-based dielectric film such as various metal oxide thin films, metal nitride thin films, etc., or a high-dielectric (high-k) film.

[0056] For reference, the metal oxide thin film or metal nitride thin film used in recent semiconductor devices may need to be uniformly deposited in a complex or deep and narrow 3D

structure. Moreover, to improve characteristics of a semiconductor device, a film may need to be formed to a thin thickness of 50 Å or less. To form such a thin thickness, generally, a metal oxide thin film or a metal nitride thin film may be deposited in an amorphous state and crystallization may be performed through a subsequent heat treatment process. However, as the thickness of the thin film decreases, a subsequent heat treatment process temperature may increase. Thus, in a deep or high 3D structure having a high-level difference and a narrow width, a defect of the bending of a structure or a bridge failure of adhering to an adjacent structure may be caused by thermal stress during a subsequent crystallization process corresponding to the heat treatment process.

[0057] To solve the foregoing problem, a method may be introduced in which a metal oxide thin film or a metal nitride thin film is formed thicker than 50 Å to reduce a crystallization temperature, thus suppressing structural defects due to thermal stress in the crystallization process. However, in this method, an etching process for reducing a metal oxide thin film or a metal nitride thin film to a required thickness, for example, 50 Å or less, may be performed, and an ALE process may be generally performed. For reference, when a metal-based dielectric film or a high-dielectric film is less than or equal to 50 Å, the crystallization temperature may be very high, such as 500° C. to 600° C. However, when the high-dielectric film is formed relatively thick exceeding 50 Å, the crystallization temperature may be lowered to 400° C. or less.

[0058] Through the fluorination process for the Al.sub.2O.sub.3 thin film, an upper portion of the Al.sub.2O.sub.3 thin film may be converted into an AlF.sub.3 thin film, as shown in FIG. 3A. Thereafter, the remaining residual gas may be purged with an inert gas such as N.sub.2, Ar, etc. After purging, the inert gas, as an exhaust gas, may be discharged to the outside of the process chamber 100 through the gas exhaust apparatus 300. For reference, the inert gas may also be referred to as a purge gas due to a purge action.

[0059] Referring to FIG. 3B, next, in a second operation of the ALE process, a gas such as TMA(Al(CH.sub.3).sub.3).sub.3, etc., may be supplied to perform a ligand exchange process. A part of a metal oxide thin film, e.g., an Al.sub.2O.sub.3 thin film, may be etched through the ligand exchange process. In FIG. 3B, a thickness removed through the ligand exchange process is indicated by A. A may be less than or equal to, for example, several Å.

[0060] Trimethylamine (TMA) is used as an example of a gas for the ligand exchange process, but the gas used in the ligand exchange process is not limited to TMA. For example, Sn(acac).sub.2, Al(CH.sub.3).sub.3).sub.2Cl, SiCl.sub.4, TiCl.sub.4, BCl.sub.3, WF.sub.6, etc., may be used as the gas for the ligand exchange process. Herein, in Sn(acac).sub.2, acac may mean CH.sub.3COCH.sub.2COCH.sub.3.

[0061] Thereafter, reaction by-products may be purged with an inert gas and discharged as an exhaust gas, completing one cycle of the ALE process. The cycle of the ALE process may be repeated several times until the metal oxide or metal nitride thin film reaches a desired thickness.

[0062] For reference, generally, a gas directly used for reaction in a corresponding process may be referred to as a source gas or a reaction gas. For example, a fluorine gas may correspond to a source gas of a fluorination process. Moreover, Sn(acac).sub.2, Al(CH.sub.3).sub.3).sub.2Cl, SiCl.sub.4, TiCl.sub.4, BCl.sub.3, WF.sub.6, etc., as well as TMA, etc., may be the source gas for the ligand exchange process. In addition, the corresponding process may further include an atmosphere gas in addition to the source gas. The atmosphere gas may include, for example, O.sub.2, O.sub.3, N.sub.2, Ar, or the like. Needless to say, the type of the atmosphere gas is not limited to the above-described gases. Moreover, to remove residual gases and by-products in a corresponding process, an inert gas such as N.sub.2, Ar, etc., may be used as a purge gas. As described above, the process gas may be a concept including a source gas, an atmosphere gas, and a purge gas, and may be used as the same concept below.

[0063] FIGS. 4A through 4C are perspective views showing in detail a shape of a nozzle in the batch-type apparatus for ALE of FIG. 1. A description will be made with reference to FIGS. 2A through 2C together.

[0064] Referring to FIG. 4A, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include a nozzle **120** for supplying the process gas into the inner tube **112**. The nozzle **120** may include a plurality of the gas injection hole **122** for injecting the process gas, as shown in FIG. 4A. The plurality of the gas injection hole **122** may be arranged at equal intervals in a vertical direction. In addition, the plurality of the gas injection hole **122** may substantially have the same size. In the vertical direction, positions of the plurality of the gas injection hole **122** in the nozzle **120** may correspond to positions between wafers that are arranged in the wafer stacking container **101**. In addition, the plurality of the gas injection hole **122** may be directed toward the center of the inner tube **112**. That is, the nozzle **120** may be arranged outside the wafer stacking container **101**, and the plurality of the gas injection hole **122** of the nozzle **120** may be directed toward a wafer arranged in the wafer stacking container **101**. In FIG. 4A, arrows may indicate a direction in which the plurality of the gas injection hole **122** is directed or a direction in which the process gas is injected, and may be directed to the wafer.

[0065] Referring to FIG. 4B, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include a nozzle **120a** for supplying the process gas into the inner tube **112**. A nozzle **120a** may include a plurality of a gas injection hole **122a**. Unlike the plurality of the gas injection hole **122** of the nozzle **120** of FIG. 4A, the plurality of the gas injection hole **122a** may increase in size in an upward direction. In FIG. 4B, the size of every three of the plurality of the gas injection hole **122a** increases in the upward direction, but an increasing pattern of the sizes of the plurality of the gas injection hole **122a** is not limited thereto. For example, the size of every two or four of the plurality of the gas injection hole **122a** or the size of each of the plurality of the gas injection hole **122a** may increase in the upward direction. In addition, the plurality of the gas injection hole **122a** may be directed toward the center of the inner tube **112**. That is, the nozzle **120a** may be arranged outside the wafer stacking container **101**, and the plurality of the gas injection hole **122a** of the nozzle **120a** may be directed toward a wafer arranged in the wafer stacking container **101**. In FIG. 4B, arrows may indicate a direction in which the plurality of the gas injection hole **122a** is directed or a direction in which the process gas is injected, and may be directed to the wafer.

[0066] For reference, as may be seen from FIG. 2A, the process gas may be supplied into the process chamber **100** through a lower portion of the process chamber **100**. Thus, a gas pressure of an upper portion of the nozzle **120a** may be lower than that of a lower portion thereof. By increasing the size of the plurality of the gas injection holes **122a** of the upper portion of the nozzle **120a**, the injection amount of the process gas may be uniform for each position in the vertical direction. As a result, due to the uniformly supplied process gas, the ALE process may be performed uniformly and smoothly on each of wafers.

[0067] Referring to FIG. 4C, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include nozzles **120** and **120b** for supplying the process gas into the inner tube **112**. The nozzles **120** and **120b** may include the plurality of gas injection holes **122**. At least one nozzle **120b** of the nozzles **120** and **120b**, for example, the nozzles **120b** on both outer sides, may have an inverted U shape in an upper portion, unlike the nozzles **120** in a center portion. The nozzles **120b** may have an inverted U shape in the upper portion, such that the injection amount of the process gas increases in the upper portion, and accordingly, the injection amount of the process gas may be uniform for each position in the vertical direction. As a result, due to the uniformly supplied process gas, the ALE process may be performed uniformly and smoothly on each of wafers. In addition, the plurality of the gas injection hole **122** may be directed toward the center of the inner tube **112**. That is, the nozzle **120** and the nozzle **120b** may be arranged outside the wafer stacking container **101**, and the plurality of the gas injection hole **122** of the nozzle **120** and the nozzle **120b** may be directed toward a wafer arranged in the wafer stacking container **101**. In FIG. 4C, arrows may indicate a direction in which the plurality of the gas injection hole **122** is directed or a direction in which the process gas is injected, and may be

directed to the wafer.

[0068] FIGS. 5A through 5C are vertical cross-sectional views showing in detail a shape of a gas outlet formed in an inner tube, in the batch-type apparatus for ALE of FIG. 1. A description will be made with reference to FIGS. 2A through 2C together.

[0069] Referring to FIG. 5A, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include the inner tube **112** in which the gas outlet **116** may be formed. In addition, a top of the inner tube **112** may have a closed structure, but is shown as an open structure in FIG. 5A for convenience of understanding. Hereinbelow, this may also be applied to FIGS. 5B and 5C.

[0070] As shown in FIG. 5A, the gas outlet **116** may be formed as a slit in the form of a line extending in the vertical direction. According to an embodiment, the gas outlet **116** may include a plurality of slits in the form of a line. For example, a plurality of slits may be arranged in the vertical direction or a plurality of slits may be arranged in an arc direction. As described with reference to FIG. 2B, the gas outlet **116** may be formed in the inner tube **112** of the second outer portion Op2 opposing the first outer portion Op1 in which the nozzle **120** is arranged.

[0071] Referring to FIG. 5B, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include an inner tube **112a** in which a gas outlet **116a** may be formed. As shown in FIG. 5B, the gas outlet **116a** may be formed as a plurality of holes arranged in the vertical direction. In FIG. 5B, the plurality of holes are arranged in one column, but the arrangement structure of the plurality of holes is not limited thereto. For example, the plurality of holes of the gas outlet **116a** may be arranged in two or more columns.

[0072] Referring to FIG. 5C, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include an inner tube **112b** in which a gas outlet **116b** may be formed. As shown in FIG. 5C, the gas outlet **116b** may be formed as a plurality of open lines arranged in the vertical direction. Each of the plurality of open lines may have a form extending in the arc direction. In the vertical direction, positions of the plurality of open lines in the inner tube **112b** may correspond to positions between wafers that are arranged in the wafer stacking container **101**.

[0073] FIGS. 6A through 6C are a perspective view, a plane view, and a partial enlarged view of a wafer stacking container, in the batch-type apparatus for ALE of FIG. 1. FIG. 6B is a plan view of a wafer stacking container of FIG. 6A from which a circular top plate is removed, viewed from top, and FIG. 6C is a partially enlarged view showing a part of a support pillar in the wafer stacking container of FIG. 6A. A description will be made with reference to FIGS. 2A through 2C together.

[0074] Referring to FIGS. 6A through 6C, in the batch-type apparatus **1000** for ALE according to an embodiment, the process chamber **100** may include the wafer stacking container **101** arranged inside the inner tube **112**. The wafer stacking container **101** may include a circular bottom plate **101bp**, three support pillars **101sp**, and a circular top plate **101tp**. The circular bottom plate **101bp** and the circular top plate **101tp** may connect the three support pillars **101sp** arranged therebetween. Thus, the circular bottom plate **101bp** and the circular top plate **101tp** may have a shape of a circular ring, instead of the shape of a circular plate. To support the shape of the circular ring, a grid, a support line, etc., may be arranged inside the circular ring.

[0075] As shown in FIG. 6B, out of the three support pillars **101sp**, two may be arranged in a portion corresponding to a diameter of the circular bottom plate **101bp** and one may be arranged between the two. The three support pillars **101sp** may be arranged in such a shape to support a wafer **500** by the three support pillars **101sp** and allow the wafer **500** to enter and exit from the wafer stacking container **101**.

[0076] As shown in FIG. 6C, a plurality of slots **sl** may be formed in each of the three support pillars **101sp**. The plurality of slots **sl** may be arranged at equal intervals in the vertical direction. The plurality of slots **sl** may face a center portion of the wafer stacking container **101**. The wafer **500** may be inserted into a slot of each of the three support pillars **101sp** and may be arranged in

the wafer stacking container **101**.

[0077] Meanwhile, the support pillars **101sp** are illustrated in the form of a cylinder, but the support pillars **101sp** are not limited to the form of a cylinder. For example, the support pillars **101sp** may have a shape of a polygonal pillar, such as a trigonal prism, a square pillar, etc., or the shape of a cylindroid. Furthermore, in the batch-type apparatus **1000** for ALE according to an embodiment, the structure of the wafer stacking container **101** is not limited to the structure shown in FIG. **6A** and may be variously changed and replaced. For example, the wafer stacking container **101** may be replaced with various other structures in which a plurality of the wafer **500** may be stacked in the vertical direction and inserted into the inner tube **112**.

[0078] FIGS. **7A** through **7C** are block diagrams of a gas supply apparatus, in the batch-type apparatus for ALE of FIG. **1**. A description will be made with reference to FIGS. **1** through **2C** together.

[0079] Referring to FIG. **7A**, in the batch-type apparatus **1000** for ALE according to an embodiment, a gas supply apparatus **200a** may include a liquid source unit **210** and a liquid delivery system (LDS) **230**. The liquid source unit **210** may store a source in a liquid state, that is, a liquid source, and supply the liquid source to the LDS **230**. The LDS **230** may be a device or a system that delivers the liquid source to the process chamber **100**. For example, the LDS **230** may include a liquid mass flow controller (LMFC) and a vaporizer. The LMFC may control the flow of the liquid source in a supply pipe, and the vaporizer may convert the liquid source into a gas source. In other words, the LDS **230** may convert a liquid source into a gas source and supply the gas source to the process chamber **100** using the LMFC and the vaporizer. The gas source may be substantially the same as the above-described source gas.

[0080] In FIG. **7A**, the gas supply apparatus **200a** is illustrated as including the liquid source unit **210**, but a source unit included in the gas supply apparatus **200a** is not limited thereto. For example, the gas supply apparatus **200a** may further include other source units that store and supply an atmosphere gas, a purge gas, etc.

[0081] Referring to FIG. **7B**, in the batch-type apparatus **1000** for ALE according to an embodiment, a gas supply apparatus **200b** may include a gas source unit **210a** and a bubbler **230a**. The gas source unit **210a** may store a source in a gas state, that is, a gas source, and supply the gas source, that is, the source gas, to the bubbler **230a**. The bubbler **230a** may be a device for delivering a gas source to the process chamber **100** and may correspond to the LDS **230** or the LMFC. In addition, a vaporizer may be unnecessary because the gas source is already in the gas state. Moreover, the gas supply apparatus **200b** according to an embodiment may also further include other source units that store and supply an atmosphere gas, a purge gas, etc.

[0082] Referring to FIG. **7C**, in the batch-type apparatus **1000** for ALE according to an embodiment, a gas supply apparatus **200c** may include a remote plasma (RP) device. More specifically, the gas supply apparatus **200c** may include an RP chamber **220** and a plasma supply pipe (PSP) **240**. In addition, although not shown, the gas supply apparatus **200c** may further include other source units that store and supply an atmosphere gas, a purge gas, etc.

[0083] The RP chamber **220**, which is a plasma chamber arranged in a position apart from the process chamber **100**, may generate plasma. For example, the RP chamber **220** may generate plasma using a fluorine gas such as NF_3 , CF_4 , etc. The PSP **240** may supply plasma generated in the RP chamber **220** to the process chamber **100**.

[0084] For reference, when plasma is generated in the RP chamber **220**, various components such as radicals, electrons, ions, ultraviolet rays, etc., may be generated. At least one of the components may be used for an etching process, a deposition process, a cleaning process, etc. Basically, a radical may be electrically neutral and an ion may electrically have a polarity. Thus, when a plasma is used for the etching process, the radical may be used for isotropic etching of an etching target and the ion may be used for anisotropic etching of the etching target. When radicals or ions are used in the etching process, components other than the corresponding component may be removed.

When the PSP **240** supplies plasma to the process chamber **100**, components unnecessary for the etching process may be removed, and only radicals or ions required for the etching process may be supplied to the process chamber **100**.

[0085] FIG. **8** is a block diagram of a gas exhaust apparatus, in the batch-type apparatus for ALE of FIG. **1**. A description will be made with reference to FIGS. **1** through **2C** together.

[0086] Referring to FIG. **8**, in the batch-type apparatus **1000** for ALE according to an embodiment, the gas exhaust apparatus **300** may include a vacuum pump **310**, a portable purge system (PPS) **320**, and a scrubber **330**. The vacuum pump **310**, which is a vacuum exhaust device, may discharge the exhaust gas in the process chamber **100** through vacuum suction. The PPS **320** is a device for burning a residual reaction gas. The scrubber **330** is a device for diluting/neutralizing a by-product gas. That is, the scrubber **330** may dilute/neutralize a harmful by-product gas of the exhaust gas. The exhaust gas may be discharged to the outside of the batch-type apparatus **1000** for ALE via the scrubber **330**.

[0087] FIGS. **9A** through **9C** are block diagrams and a conceptual view of a batch-type apparatus for ALE, according to embodiments of the present disclosure. A description will be made with reference to FIGS. **1** through **2C** together.

[0088] Referring to FIGS. **9A** and **9C**, a batch-type apparatus **1000a** for ALE according to an embodiment may be different from the batch-type apparatus **1000** for ALE of FIG. **1** in that the batch-type apparatus **1000a** includes two batch-type process chambers, for example, a first process chamber **100-1** and a second process chamber **100-2**. More specifically, the batch-type apparatus **1000a** for ALE according to an embodiment may include the first process chamber **100-1**, the second process chamber **100-2**, the gas supply apparatus **200**, and the gas exhaust apparatus **300**. The gas supply apparatus **200** is the same as described with reference to FIGS. **1** through **2C** and **7A** through **7C**. The gas exhaust apparatus **300** is the same as described with reference to FIGS. **1** through **2C** and **8**.

[0089] Each of the first process chamber **100-1** and the second process chamber **100-2** may have substantially the same structure as the process chamber **100** of the batch-type apparatus **1000** for ALE of FIG. **1**. Accordingly, the first process chamber **100-1** may include a first process tube **110-1**, a first nozzle **120-1**, and a first heater **130-1**. Accordingly, the second process chamber **100-2** may include a second process tube **110-2**, a second nozzle **120-2**, and a second heater **130-2**. In addition, each of the first process chamber **100-1** and the second process chamber **100-2** may include the wafer stacking container **101** and a chamber cover **140**, which are not shown in FIG. **9C**.

[0090] Each of the first process chamber **100-1** and the second process chamber **100-2** may perform the ALE process. Accordingly, a plurality of first nozzles **120-1** may include all four types of nozzle. Moreover, a plurality of second nozzles **120-2** may include all four types of nozzle. More specifically, in the batch-type apparatus **1000a** for ALE according to an embodiment, the process temperatures of the two operations of the ALE process, for example, the fluorination process and the ligand exchange process, may be substantially the same as each other. Accordingly, both the two-operation process may be performed in each of the first process chamber **100-1** and the second process chamber **100-2** because there is no need to change the process temperatures between the fluorination process and the ligand exchange process.

[0091] The batch-type apparatus **1000a** for ALE according to an embodiment may include the two process chambers, that is, the first process chamber **100-1** and the second process chamber **100-2**, each of which performs the ALE process, thereby maximizing the processing speed of the ALE process on the plurality of the wafer **500**. Also, the batch-type apparatus **1000a** for ALE according to an embodiment may be used when the processes of the first and second operations of the ALE process have substantially the same process temperature, and the ALE process may be performed smoothly and quickly because there is no need to change the process temperatures between the processes of the first operation and the second operation.

[0092] For reference, element **400** in FIG. **9C** may be a housing accommodating the first process chamber **100-1** and the second process chamber **100-2**. In addition, a black arrow may indicate a traveling direction of the process gas including the source gas, and a large white arrow may indicate a traveling direction of the exhaust gas discharged from each of the two process chambers, that is, the first process chamber **100-1** and the second process chamber **100-2**.

[0093] Referring to FIGS. **9B** and **9C**, a batch-type apparatus **1000b** for ALE according to an embodiment may be similar to the batch-type apparatus **1000a** for ALE of FIG. **9A** in that the batch-type apparatus **1000b** includes two process chambers, for example, a first process chamber **100a-1** and a second process chamber **100a-2**. However, the batch-type apparatus **1000b** for ALE according to an embodiment may be different from the batch-type apparatus **1000a** for ALE of FIG. **9A** in terms of a structure and an operation of each of the two process chambers, that is, the first process chamber **100a-1** and the second process chamber **100a-2**. More specifically, in the batch-type apparatus **1000b** for ALE according to an embodiment, a plurality of first nozzles **120-1** of the first process chamber **100a-1** may include three types of nozzle. For example, the plurality of first nozzles **120-1** may include the first source gas nozzle, the atmosphere gas nozzle, and the purge gas nozzle. In addition, a plurality of second nozzles **120-2** of the second process chamber **100a-2** may include three types of nozzles, but may have different types from the plurality of first nozzles **120-1**. For example, the plurality of second nozzles **120-2** may include the second source gas nozzle, the atmosphere gas nozzle, and the purge gas nozzle. Here, the first source gas nozzle may supply the first source gas used in the fluorination process, and the second source gas nozzle may supply the second source gas used in the ligand exchange process.

[0094] The batch-type apparatus **1000b** for ALE according to an embodiment may have the configurations of the first process chamber **100a-1** and the second process chamber **100a-2** described above, and the fluorination process of the ALE process is performed in the first process chamber **100a-1** and the ligand exchange process of the ALE process may be performed in the second process chamber **100a-2**. More specifically, in the batch-type apparatus **1000b** for ALE according to an embodiment, the process temperatures of the fluorination process and the ligand exchange process of the ALE process may be different from each other. Accordingly, the fluorination process may be performed in the first process chamber **100a-1** at a first process temperature, and then, the ligand exchange process may be performed in the second process chamber **100a-2** at a second process temperature. When the fluorination process is completed in the first process chamber **100a-1**, the wafer stacking container **101** containing the corresponding wafers may be moved to the second process chamber **100a-2**, and the ligand exchange process may be performed in the second process chamber **100a-2**, thus performing the ALE process.

[0095] When the batch-type apparatus **1000b** for ALE according to an embodiment include the two process chambers, that is, the first process chamber **100a-1** and the second process chamber **100a-2**, and the processes of the first and second operations of the ALE process have different process temperatures, a corresponding operation of the ALE process may be performed without changing the temperature in each of the two process chambers, that is, the first process chamber **100a-1** and the second process chamber **100a-2**. For example, the fluorination process may be performed in the first process chamber **100a-1**, and then, the ligand exchange process may be performed in the second process chamber **100a-2**. Accordingly, in the batch-type apparatus **1000b** for ALE according to an embodiment, even when the processes of the first operation and the second operation of the ALE process have different process temperatures, the processing speed of the ALE process on the plurality of the wafer **500** may be optimized and maximized.

[0096] FIGS. **10A** and **10B** are flowcharts schematically showing an ALE method based on a batch-type apparatus for ALE, according to embodiments of the present disclosure. A description will be made with reference to FIGS. **1** through **3B** together.

[0097] Referring to FIG. **10A**, in an ALE method based on a batch-type apparatus for ALE according to an embodiment (hereinafter simply referred to as an 'ALE method'), first, a

fluorination process of the ALE process is performed in operation **S110**. The fluorination process may refer to a process of converting an upper portion of a dielectric film into a metal-fluoride thin film by supplying a fluorine gas to a metal-based dielectric film, as described with reference to FIG. 3A above. As a detailed example, by supplying an HF gas to an Al.sub.2O.sub.3 thin film, a part of an upper portion of the Al.sub.2O.sub.3 thin film may be converted into an AlF.sub.3 thin film. The fluorine gas may include SF.sub.4 , XeF.sub.4 , etc., without being limited to the HF gas. [0098] On the other hand, the metal-based dielectric film such as the Al.sub.2O.sub.3 thin film may be crystallized through heat treatment before the fluorination process. In addition, in the ALE method according to the current embodiment, the metal-based dielectric film may be formed thicker than 50 Å, such that the heat treatment temperature may be relatively low. For example, the metal-based dielectric film may be crystallized at 400° C. or less. However, the crystallization temperature is not limited to the foregoing numerical values.

[0099] After the fluorination process, a first purge gas may be supplied in operation **S120**. The inside of the process chamber **100**, for example, the inner tube **112**, may be purged through the first purge gas to remove a residual gas, a by-product, etc. The first purge gas may include an inert gas, e.g., N.sub.2 , Ar, or the like.

[0100] A ligand exchange process of the ALE process may be performed in operation **S130**. The ligand exchange process may refer to a process of removing a thin film of a part of an upper portion of the dielectric film through a ligand exchange process by supplying a gas such as TMA, as described with reference to FIG. 3B above. A gas for the ligand exchange process may include Sn(acac).sub.2 , $\text{Al(CH.sub.3).sub.2Cl}$, SiCl.sub.4 , TiCl.sub.4 , BCl.sub.3 , WF.sub.6 , etc., without being limited to TMA.

[0101] After the ligand exchange process, a second purge gas may be supplied in operation **S140**. The inside of the process chamber **100**, for example, the inner tube **112**, may be purged through the second purge gas to remove a residual gas, a by-product, etc. The second purge gas may include an inert gas, e.g., N.sub.2 , Ar, or the like.

[0102] By discharging the second purge gas as an exhaust gas, the ALE process may be completed, and the part of the upper portion of the dielectric film on a semiconductor substrate may be removed. In addition, the ALE method according to an embodiment may simultaneously perform the ALE process on several wafers by using the batch-type apparatus **1000**, the batch-type apparatus **1000a**, or the batch-type apparatus **1000b** for ALE of FIGS. 1, 9A, and 9B. In addition, when the batch-type apparatus **1000b** for ALE of FIG. 9B is used, the process temperatures of the fluorination process and the ligand exchange process may be different from each other. The ALE process may be performed by performing the fluorination process in the first process chamber **100-1** and performing the ligand exchange process in the second process chamber **100-2**.

[0103] Referring to FIG. 10B, the ALE method according to an embodiment may be different from the ALE method of FIG. 10A in that the ALE method further includes operation **S150** of determining whether the thickness of the dielectric film is equal to or less than a target thickness in operation **S150**. More specifically, the ALE method according to an embodiment may include operation **S150** of determining whether the thickness of the dielectric film is less than or equal to the target thickness, after operation **S40** of supplying the second purge gas. Here, the target thickness may be, for example, 50 Å. However, the target thickness is not limited to the foregoing numerical value.

[0104] When the dielectric film is less than or equal to the target thickness (Yes), the ALE method may be terminated. However, when the thickness of the dielectric film exceeds the target thickness (No), the ALE method may proceed to operation **S110** of performing the fluorination process. Operation **S110** of performing the fluorination process through operation **S40** of supplying the second purge gas may constitute one cycle of the ALE process, and the cycle of the ALE process may be repeated until the thickness of the dielectric film reaches the target thickness.

[0105] FIG. 11 is a flowchart schematically showing a semiconductor device manufacturing

method based on a batch-type apparatus for ALE, according to embodiments of the present disclosure. A description will be made with reference to FIGS. 1 through 3B together and a description already made with reference to FIGS. 10A and 10B will be simplified or omitted. [0106] Referring to FIG. 11, in a semiconductor device manufacturing method based on a batch-type apparatus for ALE according to an embodiment (hereinafter, simply referred to as a 'semiconductor device manufacturing method'), first, a dielectric film may be formed on a semiconductor substrate in operation S10. The dielectric film may be, for example, a metal-based dielectric film such as a metal oxide thin film or a metal nitride thin film, or a high dielectric film. The dielectric film may be formed to have a relatively thick thickness exceeding, for example, 50 Å, considering a heat treatment temperature. In addition, the dielectric film may be formed in an amorphous state.

[0107] After the dielectric film is formed, the dielectric film may be crystallized by being heat-treated in operation S20. For example, the dielectric film may be crystallized by being heat-treated at a temperature of 400° C. or less.

[0108] Thereafter, the ALE process may be performed on the dielectric film in operation S100. The ALE process may be substantially the same as the ALE method described as in the description of FIG. 10A. For example, the ALE process may include operation S110 of performing the fluorination process through operation S140 of supplying the second purge gas.

[0109] Next, in operation S150, it may be determined whether the thickness of the dielectric film is less than or equal to the target thickness. Here, the target thickness may be, for example, 50 Å. However, the target thickness is not limited to the foregoing numerical value.

[0110] When the thickness of the dielectric film exceeds the target thickness (No), the semiconductor device manufacturing method may proceed to operation S100 of performing the ALE process. Operation S100 of performing the ALE process may be continuously repeated until the thickness of the dielectric film reaches the target thickness.

[0111] When the thickness of the dielectric film is less than or equal to the target thickness (Yes), a subsequent process may be performed on the semiconductor substrate in operation S200. The subsequent process may include various processes. For example, the subsequent process may include a deposition process, an etching process, an ion process, a cleaning process, etc. Herein, the deposition process may refer to a process of forming various material layers on a semiconductor substrate through chemical vapor deposition (CVD), sputtering, spin coating, etc. The etching process and the cleaning process may refer to a process of removing the entire material layer or a part thereof through etching to form a pattern. The ion process may include processes such as ion implantation, diffusion, heat treatment, etc. Through this subsequent process, integrated circuits and wirings may be formed on a semiconductor substrate to manufacture a required semiconductor device.

[0112] In addition, the subsequent process may include a process of individualizing a wafer into each semiconductor chip, and a packaging process of mounting the semiconductor chip on a PCB and sealing the same with a sealing material. In addition, the subsequent process may include a test process of testing the semiconductor device or package. By performing such subsequent processes, the semiconductor device or the semiconductor package may be completed.

[0113] While non-limiting example embodiments of the present disclosure have been particularly shown and described, it will be understood that various changes in form and details may be made without departing from the spirit and scope of the disclosure.

Claims

1. An atomic layer etching (ALE) method comprising: performing, by a batch-type apparatus for ALE, a fluorination process of an ALE process by injecting a first source gas; and performing, by the batch-type apparatus for ALE, a ligand exchange process of the ALE process by injecting a

second source gas, wherein the batch-type apparatus for ALE includes a wafer stacking container that has therein a plurality of wafers that are arranged in a vertical direction, and the batch-type apparatus for ALE further includes one or more process chambers, each of the one or more process chambers including: an inner tube that extends in the vertical direction, the inner tube configured to receive the wafer stacking container therein; a plurality of nozzles arranged in a first outer portion in the inner tube in a horizontal direction, the plurality of nozzles extending in the vertical direction and configured to supply a gas to the plurality of wafers; and a heater that surrounds the inner tube and is configured to adjust a temperature of the inner tube, wherein the performing of the fluorination process comprises supplying the first source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers, wherein the performing of the ligand exchange process comprises supplying the second source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers, wherein each of the plurality of nozzles includes a plurality of gas injection holes, the plurality of gas injection holes provided at heights corresponding to heights of the plurality of wafers, respectively, wherein the inner tube includes a gas outlet in a second outer portion in the inner tube, opposite to the first outer portion in a first horizontal direction, wherein at least one nozzle among the plurality of nozzles includes an inverted U shape in an upper portion of the at least one nozzle, and the plurality of gas injection holes of the at least one nozzle are disposed along the inverted U shape and along a portion of the at least one nozzle that extends from an end of the at least one nozzle to the upper portion of the at least one nozzle, and wherein the end of the at least one nozzle is configured to receive the gas and supply the gas to the upper portion of the at least one nozzle.

2. The ALE method of claim 1, further comprising, after the performing of the fluorination process and after the performing of the ligand exchange process, supplying a purge gas.

3. The ALE method of claim 2, wherein the inner tube is surrounded by an outer tube, and wherein the ALE method further comprises discharging the purge gas via the gas outlet of at least one from among the one or more process chambers.

4. The ALE method of claim 1, wherein the wafer stacking container includes: a bottom plate, support pillars extending from an outer portion of the bottom plate in the vertical direction and apart from one another in a direction perpendicular to the vertical direction, and a top plate connected to an upper portion of the support pillars, wherein side surfaces of the support pillars include slots that are configured to receive the plurality of wafers such that the plurality of wafers are arranged in the vertical direction, and wherein the ALE method further comprises: introducing the wafer stacking container to a bottom portion of the inner tube from an outside of the inner tube, and moving the wafer stacking container to another portion in the inner tube, before performing the fluorination process on the plurality of wafers in the wafer stacking container while the wafer stacking container is provided in the another portion in the inner tube; and moving the wafer stacking container to the bottom portion of the inner tube, from the another portion in the inner tube, and discharging the wafer stacking container to the outside of the inner tube, after the performing of the fluorination process or after the performing of the ligand exchange process.

5. The ALE method of claim 1, wherein in each of the plurality of nozzles, a size of the plurality of gas injection holes increases in an upward direction.

6. The ALE method of claim 1, wherein the ALE process comprises etching a metal oxide or a metal nitride thin film, the first source gas includes HF, SF₄, or XeF₄, and the second source gas includes Sn(acac)₂, Al(CH₃)₃, Al(CH₃)₂Cl, SiCl₄, TiCl₄, BCl₃, or WF₆.

7. The ALE method of claim 6, wherein the performing of the fluorination process and the performing of the ligand exchange process are repeated until a thickness of the metal oxide or the metal nitride thin film reaches a set target thickness.

8. The ALE method of claim 1, wherein the one or more process chambers includes a first process chamber and a second process chamber, and the fluorination process and the ligand exchange

process are each performed in the first process chamber and the second process chamber, or the fluorination process and the ligand exchange process are performed in the first process chamber and the second process chamber, respectively.

9. The ALE method of claim 1, wherein the plurality of nozzles are arranged in a second horizontal direction crossing the first horizontal direction, and the at least one nozzle having the inverted U shape further includes at least two nozzles having the inverted U shape, the at least two nozzles including: an outermost first nozzle that is farthest among the plurality of nozzles towards an end of the second horizontal direction, wherein an upper portion of the outermost first nozzle includes the inverted U shape, the inverted U shape of the outermost first nozzle being curved towards the end of the second horizontal direction; and an outermost second nozzle that is farthest among the plurality of nozzles towards an opposite end of the second horizontal direction, wherein an upper portion of the outermost second nozzle includes the inverted U shape, the inverted U shape of the outermost second nozzle being curved towards the opposite end of the second horizontal direction.

10. The ALE method of claim 9, wherein a third nozzle, among the plurality of nozzles, between the outermost first nozzle and the outermost second nozzle does not include the inverted U shape.

11. A semiconductor device manufacturing method comprising: forming a dielectric film on a semiconductor substrate; crystallizing the dielectric film through heat treatment; performing an atomic layer etching (ALE) process on the dielectric film; determining whether a thickness of the dielectric film is less than or equal to a set target thickness; and performing a subsequent process on the semiconductor substrate based on determining that the thickness of the dielectric film is less than or equal to the set target thickness, wherein the performing of the ALE process on the dielectric film comprises: performing, by a batch-type apparatus for ALE, a fluorination process of the ALE process by injecting a first source gas; supplying a first purge gas; performing, by the batch-type apparatus for ALE, a ligand exchange process of the ALE process by injecting a second source gas; and supplying a second purge gas, wherein the batch-type apparatus for ALE includes a wafer stacking container that has therein a plurality of wafers that are arranged in a vertical direction, and the batch-type apparatus for ALE further includes one or more process chambers, each of the one or more process chambers including: an inner tube that extends in the vertical direction, the wafer stacking container configured to be inserted inside the inner tube; a plurality of nozzles arranged in a first outer portion in the inner tube in a horizontal direction, the plurality of nozzles extending in the vertical direction, and configured to supply a gas to the plurality of wafers; and a heater that surrounds the inner tube and is configured to adjust a temperature of the inner tube, wherein the performing of the fluorination process comprises supplying the first source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers, wherein the performing of the ligand exchange process comprises supplying the second source gas through at least one of the plurality of nozzles of at least one from among the one or more process chambers, wherein each of the plurality of nozzles includes a plurality of gas injection holes, the plurality of gas injection holes provided at heights corresponding to heights of the plurality of wafers, respectively, wherein the inner tube includes a gas outlet in a second outer portion in the inner tube, opposite to the first outer portion in a first horizontal direction, wherein at least one nozzle among the plurality of nozzles includes an inverted U shape in an upper portion of the at least one nozzle, and the plurality of gas injection holes of the at least one nozzle are disposed along the inverted U shape and along a portion of the at least one nozzle that extends from an end of the at least one nozzle to the upper portion of the at least one nozzle, and wherein the end of the at least one nozzle is configured to receive the gas and supply the gas to the upper portion of the at least one nozzle.

12. The semiconductor device manufacturing method of claim 11, wherein the dielectric film includes a metal oxide or a metal nitride thin film, the first source gas includes HF, SF₆, or XeF₄, and the second source gas includes Sn(acac)₂, Al(CH₃)₃, Al(CH₃)₂Cl, SiCl₄, TiCl₄, BCl₃, or WF₆.

13. The semiconductor device manufacturing method of claim 11, wherein the one or more process chambers includes a first process chamber and a second process chamber, and the fluorination process and the ligand exchange process are each performed in the first process chamber and the second process chamber, or the fluorination process and the ligand exchange process are performed in the first process chamber and the second process chamber, respectively.

14. The semiconductor device manufacturing method of claim 11, wherein the plurality of nozzles are arranged in a second horizontal direction crossing the first horizontal direction, and the at least one nozzle having the inverted U shape further includes at least two nozzles having the inverted U shape, the at least two nozzles including: an outermost first nozzle that is farthest among the plurality of nozzles towards an end of the second horizontal direction, wherein an upper portion of the outermost first nozzle includes the inverted U shape, the inverted U shape of the outermost first nozzle being curved towards the end of the second horizontal direction; and an outermost second nozzle that is farthest among the plurality of nozzles towards an opposite end of the second horizontal direction, wherein an upper portion of the outermost second nozzle includes the inverted U shape, the inverted U shape of the outermost second nozzle being curved towards the opposite end of the second horizontal direction.

15. The semiconductor device manufacturing method of claim 14, wherein a third nozzle, among the plurality of nozzles, that is between the outermost first nozzle and the outermost second nozzle does not include the inverted U shape.
