

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250279319

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

LIN; Yung-Chen et al.

TWO-DIMENSION SELF-ALIGNED SCHEME WITH SUBSTRUCTIVE METAL ETCH

Abstract

Embodiments of the present disclosure generally relate to layer stacks produced during back-end-of-line (BEOL) process flows. In one or more embodiments, the layer stack is disposed on a substrate and contains a first hard mask layer disposed on a first metal layer, one or more low-k material layers disposed over the first hard mask layer, a second metal layer disposed over the one or more low-k material layers and the first hard mask layer, a second hard mask layer disposed over the second metal layer, and an oxide layer disposed over the second hard mask layer. The second metal layer, the second hard mask layer, and the oxide layer are patterned and form a plurality of features. A gapfill interconnect metal is connected to the first metal layer and the second metal layer and is disposed through the first hard mask layer and the one or more low-k material layers.

Inventors: LIN; Yung-Chen (Gardena, CA), LANG; Chi-I (Cupertino, CA), HWANG; Ho-Yung (Cupertino, CA)

Applicant: Applied Materials, Inc. (Santa Clara, CA)

Family ID: 85038347

Appl. No.: 19/207329

Filed: May 13, 2025

Related U.S. Application Data

parent US division 17859838 20220707 parent-grant-document US 12327764 child US 19207329
us-provisional-application US 63296437 20220104
us-provisional-application US 63227821 20210730

Publication Classification

Int. Cl.: H01L21/768 (20060101); H01L21/033 (20060101); H01L23/522 (20060101)

U.S. Cl.:

CPC **H01L21/76897** (20130101); **H01L21/0332** (20130101); **H01L21/0335** (20130101);
H01L21/0337 (20130101); **H01L21/0338** (20130101); **H01L23/5226** (20130101);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This application is a divisional of U.S. application Ser. No. 17/859,838, filed on Jul. 7, 2022, which claims benefit to U.S. Prov. Appl. No. 63/227,821, filed on Jul. 30, 2021, and U.S. Prov. Appl. No. 63/296,437, filed on Jan. 4, 2022, which are herein incorporated by reference in their entirety.

BACKGROUND

Field

[0002] Embodiments of the present disclosure generally relate to fabrication of microelectronic devices, and more specifically, relate to back end of line (BEOL) processes during the fabrication of microelectronic devices.

Description of the Related Art

[0003] Integrated circuits are made possible by processes which produce intricately patterned material layers on substrate surfaces. Producing patterned material on a substrate requires controlled methods for deposition and removal of material. Plasma dry etching is used for a variety of purposes including transferring a pattern in photoresist into underlying layers, thinning layers, or thinning lateral dimensions of features already present on the surface. In some embodiments, etching is performed through a hard mask to improve etch accuracy. Layer formation and etching is performed to achieve desired end device structures.

[0004] As a result of the diversity of materials, circuits, and processes, the layer formation and etch operations have become increasingly complex, the size of device features has been reduced, and more complex device structures are needed. As device structures become more complex, alignment of features within the layers has become increasingly difficult. This is further complicated as the desired feature size has decreased.

[0005] Therefore, there is a need for a method to perform back end of line (BEOL) processes which improve the accuracy and alignment of etching operations.

SUMMARY

[0006] The present disclosure generally relates to a method of processing a substrate. The method is suitable for semiconductor manufacturing, such as manufacturing of logic or memory semiconductor devices. The method includes depositing a first oxide layer over a patterned hard mask layer. A first portion of a via is etched through the first oxide layer and through an opening within the patterned hard mask layer. A second portion of the via is etched through an upper metal layer and one or more low-k material layers to expose a portion of a lower metal layer. The one or more low-k material layers are disposed between the upper metal layer and the lower metal layer. The second portion of the via is gap-filled with a gapfill metal. The first portion of the via is filled with a second oxide layer. A portion of the first oxide layer and the second oxide layer is removed to form a patterned layer. The patterned hard mask layer is removed to form openings within the patterned layer. A portion of the upper metal layer is etched through the openings within the patterned layer after removing the patterned hard mask layer.

[0007] In another embodiment, a method of processing a substrate, suitable for semiconductor manufacturing, includes depositing a low temperature oxide layer over a patterned hard mask layer. The patterned hard mask layer includes a plurality of openings and the low temperature oxide layer is disposed within the plurality of openings. A first portion of a via is etched through the low

temperature oxide and through an opening within the patterned hard mask layer. A second portion of the via is etched through an upper metal layer, an insulating layer, a low-k layer, and a blocking layer to expose a portion of a lower metal layer. The second portion of the via is gap-filled with a gapfill metal to connect the upper metal layer and the lower metal layer.

[0008] In yet another embodiment, a layer stack disposed on a substrate, suitable for use as a semiconductor, is described. The layer stack includes a first metal layer. A first hard mask layer is disposed on the first metal layer. One or more low-k material layers are disposed over the first hard mask layer. A second metal layer is disposed over the one or more low-k material layers and the first hard mask layer. A second hard mask layer is disposed over the second metal layer. An oxide layer is disposed over the second hard mask layer. Each of the second metal layer, the second hard mask layer, and the oxide layer are patterned and form a plurality of features. A gapfill metal connects the first metal layer and the second metal layer and is disposed through an opening within the first hard mask layer and the one or more low-k material layers.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] So that the manner in which the above recited features of the present disclosure can be understood in detail, a more particular description of the disclosure, briefly summarized above, may be had by reference to embodiments, some of which are illustrated in the appended drawings. It is to be noted, however, that the appended drawings illustrate only exemplary embodiments and are therefore not to be considered limiting of the scope of the disclosure, as the disclosure may admit to other equally effective embodiments.

[0010] FIGS. 1A-1C depict schematic cross-sectional first side views of a layer stack, according to one or more embodiments described and discussed herein.

[0011] FIGS. 2A-2I depict schematic cross-sectional second side views of the layer stack of FIGS. 1A-1C, according to one or more embodiments described and discussed herein.

[0012] FIG. 3 is a flow chart depicting a method for forming the layer stack of FIGS. 1A-1C, according to one or more embodiments described and discussed herein.

[0013] FIG. 4 is a flow chart depicting a method for forming the layer stack of FIGS. 2A-2I, according to one or more embodiments described and discussed herein.

[0014] To facilitate understanding, identical reference numerals have been used, where possible, to designate identical elements that are common to the figures. It is contemplated that elements and features of one embodiment may be beneficially incorporated in other embodiments without further recitation.

DETAILED DESCRIPTION

[0015] The present disclosure generally relates to a method for forming a semiconductor device. The method is more specifically directed towards the formation of a layer stack during a back-end-of-line (BEOL) process flow. The method utilizes a 2-dimensional (2D) self-aligned scheme with a subtractive metal etch. The methods described herein enable 2D self-alignment of a via to both a first metal layer and a second metal layer formed as separate layers within the layer stack. The methods described herein are compatible with current dual damascene self-aligned titanium nitride hard mask patterning. The methods described herein are beneficial for small pitch patterning, such as ultra-small pitch patterning. Ultra-small pitch patterning includes pitch patterning of less than or about 22 nm, such as less than or about 20 nm, such as less than or about 18 nm, such as less than or about 15 nm.

[0016] The methods described herein further include a first self-aligned double patterning process and a subtractive metal etch of a first metal layer within a lower portion of a film stack. A silicon nitride hard mask layer is disposed on top of the first metal layer and is used as a chemical

mechanical polishing (CMP) stop layer. Once the features formed during the subtractive metal etch have been filled with a gap-fill material, an upper portion of the film stack is formed over the lower portion. The upper portion includes a second metal layer.

[0017] Once the upper portion is formed on the lower portion, a second self-aligned double patterning process is performed. The second self-aligned double patterning process includes transferring a pattern into a titanium nitride or a tungsten carbide hard mask layer. The titanium nitride or tungsten carbide hard mask layer is disposed on top of the second metal layer and an upper silicon nitride hard mask layer. Via patterning is performed through openings within the titanium nitride or tungsten carbide hard mask layer to form one or more vias. Via patterning etches through each of the upper silicon nitride hard mask layer, the second metal layer, and one or more additional layers disposed between the second metal layer and the first metal layer. Via patterning exposes a portion of the first metal layer. The alignment of the one or more vias to the first metal layer is achieved using selective etch of the silicon nitride performed during earlier operations, while the use of the titanium nitride or tungsten carbide mask aligns the via etch with the second metal layer.

[0018] A lower portion of the one or more vias is filled with a metal gapfill material to connect the first metal layer and the second metal layer. A metal etching process is used to adjust the height of the metal gapfill material in the via. An upper portion of the one or more vias is filled with a low temperature oxide. The low temperature oxide is utilized to reverse the tone of the titanium nitride or tungsten carbide mask, such that the titanium nitride or tungsten carbide mask is removed to leave the reverse tone low temperature oxide pattern. The reverse tone low temperature oxide pattern is utilized to etch the second metal layer and form a plurality of features.

[0019] FIGS. 1A-1C illustrate schematic cross-sectional first side views of a layer stack **100**. FIG. 3 illustrates a first method **300** of forming the layer stack **100** of FIGS. 1A-1C, according to one or more embodiments. In the following description, the layer stack **100** and the first method **300** of forming the layer stack **100** are described together with reference to the respective FIGS. 1A-1C and FIG. 3. The layer stack **100** is formed on top of a substrate **101**. The substrate **101** includes a plurality of layers. The substrate **101** includes a plurality of front end of line (FEOL) layers **102** and a plurality of middle of line (MOL) layers **104**. The FEOL layers **102** include transistors, capacitors, or other layers formed during FEOL processing. The MOL layers **104** include contact structures configured to be disposed between the FEOL layers **102** and a plurality of back-end of line (BEOL) layers. The MOL layers **104** are disposed on top of the FEOL layers **102**.

[0020] The layer stack **100** further includes a first metal layer **106** disposed on top of the substrate **101**. A first hard mask layer **108** is disposed on top of the first metal layer **106**. The first hard mask layer **108** is patterned and forms a first hard mask **107**. The first hard mask **107** includes a plurality of openings **112** disposed therein. In some embodiments, the first metal layer **106** and the first hard mask layer **108** are described as a lower metal layer or a lower hard mask layer respectively.

[0021] The first metal layer **106** is a transition metal layer. In some embodiments, the first metal layer **106** includes ruthenium, molybdenum, tungsten, alloys thereof, or any combination thereof. In one or more embodiments, the first metal layer **106** is an alloy of one of ruthenium, molybdenum, or tungsten. In other embodiments, the first hard mask layer **108** is a nitride layer, such as a silicon nitride layer.

[0022] Referring to FIG. 3 and FIG. 1A, during an operation **302** of the first method **300**, the first metal layer **106** is patterned through the first hard mask **107** to form a plurality of first metal features **105**. The first metal features **105** include the plurality of openings **112** disposed therebetween. The first metal features **105** and the first hard mask **107** form a plurality of first features **109**. The plurality of first features **109** include one of the plurality of openings **112** disposed between each adjacent first feature **109**. The plurality of first features **109** have a first feature pitch. The first feature pitch is less than or about 25 nm, such as less than or about 20 nm, such as less than or about 18 nm, such as less than or about 15 nm.

[0023] Referring further to FIG. 1B, during another operation 304, the openings 112 between the first features 109 are filled with a low-k material 114, such that the low-k material 114 is deposited within each opening 112 between each of the first metal features 105 and the openings 112 within the first hard mask 107. The low-k material 114 is a material with a dielectric constant of less than or about 4, such as less than or about 3.5, such as less than or about 3. The low-k material 114 may include silicon dioxide (SiO₂), doped silicon dioxide, carbon doped silicon dioxide, or combinations thereof.

[0024] Once the low-k material 114 has been deposited during the operation 304, a top surface 110 of the first hard mask layer 108 and the low-k material 114 are polished during an operation 306. The polishing of the first hard mask layer 108 and the low-k material 114 during an operation 306 planarizes the first hard mask layer 108 and the low-k material 114. The polishing during the operation 306 may be a chemical mechanical polishing (CMP). The thickness of the first hard mask layer 108 may be reduced during the operation 306, such that the thickness of the first hard mask layer 108 decreases by about 1 nm to about 10 nm, such as about 2 nm to about 8 nm, such as about 4 nm to about 6 nm. At least a portion of the first hard mask layer 108 is kept after the polishing operation to protect the first metal layer 106.

[0025] After planarization of the first hard mask layer 108 and the low-k material 114, a blocking layer 120 is deposited on top of the planar top surface 110 of the first hard mask layer 108 and the low-k material 114 during an operation 308. The blocking layer 120 is configured to cap the low-k material 114 and the first hard mask layer 108 to prevent the exposure of the low-k material and the first hard mask layer 108 to moisture. The blocking layer 120 further provides a uniform layer for subsequent layer growth. The blocking layer 120 may be a metal oxide layer, such as an aluminum oxide layer or a gallium oxide layer. The blocking layer 120 may further be a metal nitride layer, such as aluminum nitride, or silicon carbon-nitride. In some embodiments, the blocking layer 120 is a metal oxide and metal nitride layer stack, such as one or more alternating layers of aluminum oxide and aluminum nitride.

[0026] The first metal layer 106 has a first thickness T_{sub.1} after formation of the blocking layer 120. The first thickness T_{sub.1} is about 15 nm to about 40 nm, such as about 20 nm to about 35 nm, such as about 20 nm to about 30 nm, such as about 25 nm. The first hard mask layer 108 has a second thickness T_{sub.2} after formation of the blocking layer 120. The second thickness T_{sub.2} is about 1 nm to about 15 nm, such as about 4 nm to about 12 nm, such as about 5 nm to about 10 nm, such as about 5 nm. The blocking layer 120 has a third thickness T_{sub.3} after the operation 308. The third thickness T_{sub.3} is less than or about 10 nm, such as about 0.5 nm to about 10 nm, such as about 1 nm to about 5 nm, such as about 2 nm to about 4 nm, such as about 3 nm. In some embodiments, the third thickness T_{sub.3} is less than or about 3 nm, such as less than or about 2 nm.

[0027] Referring further to FIG. 1C, the blocking layer 120, the first hard mask layer 108, the first metal layer 106, the MOL layers 104, and the FEOL layers 102 form a lower portion 116 of the layer stack 100. An upper portion 118 is formed on top of the lower portion 116 after the deposition of the blocking layer 120 during the operation 308. The upper portion 118 includes a low-k layer 122, an insulation layer 124, a second metal layer 126, a second hardmask layer 128, and a third hardmask layer 130.

[0028] The upper portion 118 is formed by first depositing the low-k layer 122 on top of the blocking layer 120 during an operation 310. The low-k layer 122 is deposited directly on top of the blocking layer 120. The low-k layer 122 has a dielectric constant of less than or about 4, such as less than or about 3.5, such as less than or about 3. The low-k layer 122 may include silicon dioxide (SiO₂), doped silicon dioxide, and/or carbon doped silicon dioxide. The low-k layer 122 is a porous material. The low-k layer 122 has a dielectric constant of less than or about 3.5, such as less than or about 3, such as about 2.3 to about 3. In some embodiments, the dielectric constant of the low-k layer 122 is less than or about 2.3.

[0029] After depositing the low-k layer **122** during the operation **310**, the insulation layer **124** is deposited on top of the low-k layer **122** during an operation **312**. The insulation layer **124** is a second low-k layer and is deposited directly on the low-k layer **122**. The insulation layer **124** has a higher density than the low-k layer **122** and therefore reduces metal diffusion into the low-k layer **122** from the second metal layer **126** disposed above the insulation layer **124**. Both of the low-k layer **122** and the insulation layer **124** increase the capacitance of the structure within the layer stack **100**. The insulation layer **124** is a low-temperature oxide layer. The insulation layer **124** has a dielectric constant of less than or about 4, such as less than or about 3.5, such as less than or about 3. The insulation layer **124** may include silicon oxycarbide, silicon oxycarbonitride, boron nitride, tetraethyl orthosilicate (TEOS), dopants thereof, or any combination thereof. In some embodiments, the insulation layer **124** and the low-k layer **122** are referred together as one or more low-k material layers. In some embodiments, additional low-k material layers may be disposed between the blocking layer **120** and the second metal layer **126**.

[0030] The second metal layer **126** is disposed on top of the insulation layer **124** during another operation **314**. The second metal layer **126** is disposed directly on top of the insulation layer **124**. The second metal layer **126** is a similar material to the first metal layer **126**, such that the second metal layer **126** includes ruthenium, molybdenum, tungsten, alloys thereof, or any combination thereof. In some embodiments, the second metal layer **126** is an alloy of one of ruthenium, molybdenum, or tungsten. The second metal layer **126** is a continuous layer disposed over the insulation layer **124**.

[0031] After the formation of the second metal layer **126** during the operation **314**, the second hard mask **128** is deposited on top of the second metal layer **126** during another operation **316**. The second hard mask **128** is a similar material to the first hard mask **108**, such that the second hard mask **128** includes a nitride layer, such as a silicon nitride layer. The second hard mask **128** is a continuous layer during and immediately following deposition during the operation **316**. In some embodiments, the second metal layer **126** and the second hard mask layer **128** are described as an upper metal layer or an upper hard mask layer respectively. The second hard mask **128** serves as an under stop layer, such as an etch stop layer to stop the etch of the third hard mask **130** before transferring of the pattern of the third hard mask **130** through the layer stack **100**.

[0032] The third hard mask **130** is deposited on top of the second hard mask **128** during an operation **318**. The third hard mask **130** is disposed directly on top of the second hard mask **128**. The third hard mask **130** is a nitride or a carbide hard mask. In some embodiments, the third hard mask **130** is a titanium nitride or a tungsten carbide hard mask. In some embodiments, the third hard mask **130** is a metal carbide which is easy to remove with a wet etch process, such as a titanium nitride (TiN), a tungsten carbide (WC), a titanium carbide (TiC), or a ruthenium carbide (RuC) hard mask.

[0033] After depositing the third hard mask **130**, the third hard mask **130** is patterned during an operation **320**. Patterning the third hard mask **130** may be performed by exposing portions of the third hard mask **130** to one or more radiation sources. Patterning the third hard mask **130** further includes removing portions of the third hard mask **130** to form openings **132**. The openings **132** are disposed through the third hard mask **130** and expose a top surface **136** of the second hard mask **128**. Therefore, the openings **132** extend from the top surface **134** of the third hard mask **132** to the top surface **136** of the second hard mask **128**. In some embodiments, the third hard mask **130** is patterned using a lithographic process.

[0034] After formation of the third hard mask **130**, the low-k layer has a fourth thickness $T_{sub.4}$. The fourth thickness $T_{sub.4}$ is about 3 nm to about 20 nm, such as about 5 nm to about 15 nm, such as about 7 nm to about 13 nm, such as about 10 nm. After formation of the third hard mask **130**, the insulation layer **124** has a fifth thickness $T_{sub.5}$. The fifth thickness $T_{sub.5}$ is about 3 nm to about 20 nm, such as about 5 nm to about 15 nm, such as about 7 nm to about 13 nm, such as about 10 nm. After formation of the third hard mask **130**, the second metal layer **126** has a sixth

thickness T.sub.6. The sixth thickness T.sub.6 is about 15 nm to about 40 nm, such as about 20 nm to about 35 nm, such as about 20 nm to about 30 nm, such as about 25 nm. After formation of the third hard mask **130**, the second hard mask **128** has a seventh thickness T.sub.7. The seventh thickness T.sub.7 is about 2 nm to about 20 nm, such as about 5 nm to about 15 nm, such as about 8 nm to about 13 nm, such as about 10 nm. The third hard mask **130** has an eighth thickness T.sub.8. The eighth thickness T.sub.8 is about 5 nm to about 40 nm, such as about 10 nm to about 30 nm, such as about 15 nm to about 25 nm, such as about 20 nm.

[0035] FIGS. **1A-1C** illustrate the layer stack **100** in a first orientation, such that the layer stack **100** is being viewed through an x-z plane, where a y-direction is orthogonal to each of the x-direction and the z-direction. When viewed through a y-z plane (FIG. **2A**), additional openings **202** within the third hard mask **130** are viewed. The openings **202** are disposed from the top surface **134** of the third hard mask **132** to the top surface **136** of the second hard mask **128**. The openings **202** are disposed between portions **204** of the third hard mask **130**, such that each portion **204** includes a sidewall **206** extending from the top surface **134** of the third hard mask **132** to the top surface **136** of the second hard mask **128**.

[0036] FIGS. **2A-2I** illustrate schematic cross-sectional second side views of the layer stack **100** of FIGS. **1A-1C** through the y-z plane. FIG. **4** illustrates the method **400** of forming the layer stack **100** of FIGS. **2A-2I**. After the method **300** of FIG. **3** and the patterning of the third hard mask **130**, the method **400** is performed on the layer stack **100** to form an interconnect **220** (FIG. **2E**) between the first metal layer **106** and the second metal layer **126** and a plurality of second features **232** (FIG. **2I**).

[0037] Referring to FIG. **4** and FIG. **2B**, after formation of the pattern of the third hard mask **130**, a low temperature oxide layer **208** is deposited over the patterned third hard mask **130** during an operation **402**. The low temperature oxide layer **208** fills each of the openings **202** between each portion **204** of the third hard mask **130**. The low temperature oxide layer **208** is grown to be formed completely over the patterned third hard mask **130**, such that the low temperature oxide layer **208** encapsulates the patterned third hard mask **130**. The portion **205** of the low temperature oxide layer **208** disposed within each of the openings **202** forms a reverse tone mask from the third hard mask **130**. The low temperature oxide layer **208** directly contacts the top surface **136** of the second hard mask **128** as well as the sidewalls **206** and top surface **134** of the third hard mask **130**.

[0038] The low temperature oxide layer **208** is sometimes referred to as an oxide layer **208**. The low temperature oxide layer **208** includes a low temperature oxide material. The low temperature oxide layer **208** is deposited using a low-temperature process, such that the process volume and the substrate are heated to or maintained at a temperature of less than or about 400° C., such as less than or about 300° C., such as less than or about 200° C. The low temperature oxide layer **208** is deposited at a low temperature to reduce warpage of the layer stack **100** and the third hard mask **130**. The low temperature oxide layer **208** is easy to reflow and assists in forming a planar top surface.

[0039] After depositing the low temperature oxide layer **208** during the operation **402**, a photoresist layer **210** is deposited over the low temperature oxide layer **208** as shown in FIG. **2C**. The photoresist layer **210** is a tri-layer photoresist layer, such that the photoresist layer **210** includes a bottom layer of a spin on carbon material, a back anti-reflection coating (BARC) or a silicon anti-reflection coating (SiARC) disposed on the spin on carbon material, and an extreme ultra violet (EUV) photoresist layer or metal resist layer disposed on top of the BARC/SiARC layer. The photoresist layer **210** is deposited on top of the low temperature oxide layer **208**, such that the photoresist layer **210** is in contact with the low temperature oxide layer **208**.

[0040] At least a portion of the photoresist layer **210** is exposed using a lithographic process during an operation **406**. The exposure of the photoresist layer **210** includes exposing portions of the photoresist layer **210** to radiation. After exposure, the photoresist layer **210** includes a plurality of unexposed portions **212** and one or more exposed portions **214**. The exposed portions **214** may be

cross-linked during exposure and later removed if the photoresist layer **210** is a negative tone resist. In embodiments wherein the photoresist layer **210** is a positive tone resist, the exposed portions **214** and the unexposed portions **212** are switched and the unexposed portions **212** are removed.

[0041] Referring further to FIG. 2D, after exposing the photoresist layer **210**, a portion, such as the exposed portion **214**, of the photoresist layer **210** may be removed and a via **215** is etched through the opening formed within the photoresist layer **210** and the openings **202** within the third hard mask **130** during an operation **408**. Etching the via **215** includes etching a portion of the low temperature oxide layer **208** disposed above two adjacent portions **204** of the third hard mask **130** as well as a portion of the low temperature oxide layer **208** disposed between sidewalls of two adjacent portions **204** of the third hard mask **130**. The third hard mask **130** serves to align the via **215** etch and reduces the width of the via **215**. The width of the via **215** is reduced from an upper portion **216** of the via **215** disposed above the third hard mask **130** to a lower portion **218** of the via **215** disposed between the sidewalls **206** of adjacent portions **204** of the third hard mask **130**. Therefore, the upper portion **216** of the via **215** has a first width $W_{sub.1}$. The first width $W_{sub.1}$ is greater than about 12 nm, such as about 15 nm to about 25 nm, such as about 17 nm to about 23 nm, such as about 18 nm to about 20 nm. The lower portion **218** of the via **215** has a second width $W_{sub.2}$. The second width $W_{sub.2}$ is less than 75% of the first width $W_{sub.1}$, such that the second width $W_{sub.2}$ is about 50% of the first width $W_{sub.1}$, such that the second width $W_{sub.2}$ is considered a half-pitch of the pitch of the upper portion **216**. The second width $W_{sub.2}$ is less than or about 20 nm, such as less than or about 18 nm, such as less than or about 15 nm, such as less than or about 12 nm, such as less than or about 11 nm. The second width $W_{sub.2}$ is the distance between the sidewalls **206** of adjacent portions **204** of the third hard mask **130**. In some embodiments, when the first width $W_{sub.1}$ is about 22 nm, such second width $W_{sub.2}$ is about 11 nm and when the first width $W_{sub.1}$ is about 18 nm, the second width $W_{sub.2}$ is about 9 nm.

[0042] The lower portion **218** of the via **215** extends from the third hard mask **130**, through the second hard mask layer **128**, through the second metal layer **126**, through the insulation layer **124**, through the low-k layer **122**, through the blocking layer **120**, and through the first hard mask layer **108**. The lower portion **218** of the via **215** extends to the first metal layer **106**, such that a portion of the top surface of the first metal layer **106** is exposed or the via **215** is formed through a portion of the first metal layer **106**. The via **215** is formed using one or more etch operations, such as a dry etch, a wet etch, or a plasma operation. After formation of the via **215**, the photoresist layer **210** is removed via a selective etch or a development process operation. In some embodiments, the upper portion **216** of the via **215** is referred to as a first portion of the via **215** while the lower portion **218** of the via **215** is referred to as a second portion of the via **215**.

[0043] Referring further to FIG. 2E, once the via **215** is etched to contact the first metal layer **106**, a metal material is gap-filled into the lower portion **218** of the via **215** during an operation **410** to form an interconnect **220** between the first metal layer **106** and the second metal layer **126**. The metal material is a similar material to the first metal layer **106** and/or the second metal layer **126**. The metal material fills the lower portion **218** of the via **215** until the metal material reaches the second hard mask layer **128** or the third hard mask layer **130** as shown in FIG. 2E. Therefore, the metal material does not fill the upper portion **216** of the via **215**. The metal material includes ruthenium, molybdenum, tungsten, alloys thereof, or any combination thereof. In some embodiments, the metal material is an alloy of one of ruthenium, molybdenum, or tungsten. In some embodiments, the metal material fills the entire lower portion **218** of the via **215**. A metal etching process is used to adjust the height of the metal gapfill material in the via **215**, such that the metal material is disposed below the top surface of the second hard mask layer **128** and the third hard mask layer **130**, but within the second metal layer **126**.

[0044] After the metal material fills the lower portion **218** of the via **215**, the substrate **101** and the layer stack **100** are annealed during an operation **412**. The anneal of the layer stack **100** includes heating the layer stack **100** and the substrate **101** to an anneal temperature of about 100° C. to about

700° C., such as about 200° C. to about 500° C., such as about 200° C. to about 400° C., such as about 300° C. to about 400° C. Annealing the layer stack **100** reduces the number of voids and grain boundaries within the interconnect **220**, between the interconnect **220** and the first metal layer **106**, and between the interconnect **220** and the second metal layer **126**. The anneal operation may further reduce the resistivity of the interconnect **220** and the boundary between the interconnect **220** and either of the first metal layer **106** or the second metal layer **126**. The annealing of the layer stack **110** may further reduce one or more of resistivity or stress within other layers formed during the method **300** of FIG. 3 and the method **400** of FIG. 4. The annealing of the layer stack **110** is performed after the formation of the via **216** and the filling of the via **215** with the metal material. [0045] Referring further to FIG. 2F, after forming the interconnect **220** and annealing the layer stack **100**, a low temperature oxide **222** is deposited into the unfilled portion of the via **215**, such as the upper portion **216** of the via **215**, during an operation **414**. The low temperature oxide **222** deposited during the operation **414** is similar to the low temperature oxide **222** of the low temperature oxide layer **208** and fills the gap formed in the low temperature oxide layer **208** during the formation of the via **215** as shown in FIG. 2F. The low temperature oxide **222** fills the opening within the second hard mask layer **128** formed by the via **215**. The low temperature oxide **222** further fills the opening formed between the sidewalls **206** of the third hard mask **130** during formation of the via **215**.

[0046] After the low temperature oxide is utilized to fill the upper portion **216** of the via **215**, an upper portion **223** of the low temperature oxide layer **208** is removed during an operation **416**. Removing the upper portion **223** is performed using one or a combination of an etch operation or a polishing operation. In some embodiments, the upper portion **223** is removed using CMP. The upper portion **223** is the portion of the low temperature oxide layer **208** disposed above the third hard mask layer **130**. The low temperature oxide layer **208** is removed until the top of the third hard mask **130** is exposed as shown in FIG. 2G. The top surfaces of the low temperature oxide layer **208** and the third hard mask **130** are co-planar, such that the low temperature oxide layer **208** forms a reverse tone hard mask from the third hard mask **130**. The remaining portion **224** of the low temperature oxide layer **208** and the remaining portion **226** of the low temperature oxide introduced during the operation **414** form a patterned layer which is a reverse tone hard mask of the third hard mask **130**.

[0047] Referring further to FIG. 2H, after formation of the patterned layer and the reverse tone hard mask, the remaining portions of the third hard mask **130** are removed during an operation **418**. Removing the remaining portions of the third hard mask **130** reverses the pattern of the hard mask and leaves the remaining portions **224**, **226** of the low temperature oxide layer **208** as the patterned layer. Removing the third hard mask **130** provides openings **230** between each of the remaining portions **224**, **226**.

[0048] Referring further to FIG. 21, a portion of the second hard mask **128** and the second metal layer **126** are etched through the openings **230** of the reverse tone hard mask, formed by the low temperature oxide layer **208**, during an operation **420**. Etching the second metal layer **126** and the second hard mask **128** is performed using a selective etch process. The etching the second metal layer **126** and the second hard mask **128** is performed using a dry etch, a wet etch, or a plasma etch process. Etching the second hard mask **128** and the second metal layer **126** through the openings **230** forms a plurality of second features **232** as shown in FIG. 21. The plurality of second features **232** include second metal features **234** and second hard mask features **236**. The pattern of the second metal features **234** and the second hard mask features **236** is determined by the pattern of the temperature oxide layer **208**. Each of the second features **232** are separated by a gap **238** disposed therebetween. In some embodiments, the plurality of first features **109** and the plurality of second features **232** form gratings within the layer stack **100**. The plurality of second features **232** have a second feature pitch. The second feature pitch is less than or about 25 nm, such as less than or about 20 nm, such as less than or about 18 nm, such as less than or about 15 nm.

[0049] It is contemplated additional metal layers, low-k material layers, and hard masks may be utilized in addition to those illustrated herein. The additional metal layers, low-k material layers, and hard masks form larger stacks of interconnected metal layers.

[0050] The methods described herein enable a device structure with an interconnect **220** between a first metal layer **106** and a second metal layer **126** separated by one or more low-k material layers **122**, **124**. Each of the first metal layer **106** and the second metal layer **126** include a plurality of first features **109** or second features **232**. The methods described herein enable self-alignment of the metal interconnect **220** with the first features **109** of the first metal layer **106** and the second features **232** of the second metal layer **126**. The methods described herein further enable reduced interconnect **220** width.

[0051] Each of the deposition operations may be one or a combination of chemical vapor deposition (CVD), physical vapor deposition (PVD), plasma enhanced chemical vapor deposition (PE-CVD), and atomic layer deposition (ALD). In some embodiments, the layers are spray coated or spin coated onto the layer stack **100**. Each of the etch or removal operations may be one or a combination of a wet etch, a dry etch, or a plasma etch. In some embodiments, one or more layers are removed using a development and dissolution process.

[0052] Embodiments of the present disclosure further relate to any one or more of the following examples:

[0053] 1. A method of processing a substrate, suitable for semiconductor manufacturing, comprising: depositing a first oxide layer over a patterned hard mask layer; etching a first portion of a via through the first oxide layer and through an opening within the patterned hard mask layer; etching a second portion of the via through an upper metal layer and one or more low-k material layers to expose a portion of a lower metal layer, the one or more low-k material layers disposed between the upper metal layer and the lower metal layer; gap-filling the second portion of the via with a gapfill metal; filling the first portion of the via with a second oxide layer; removing a portion of the first oxide layer and the second oxide layer to form a patterned layer; removing the patterned hard mask layer to form openings within the patterned layer; and etching a portion of the upper metal layer through the openings within the patterned layer after removing the patterned hard mask layer.

[0054] 2. The method according to example 1, wherein a first hard mask is disposed between the lower metal layer and the one or more low-k material layers and a second hard mask is disposed between the upper metal layer and the patterned hard mask layer.

[0055] 3. The method according to example 2, wherein the first hard mask layer and the second hard mask layer are silicon nitride layers.

[0056] 4. The method according to any one of examples 1-3, wherein the patterned hard mask layer is a titanium nitride or a tungsten carbide hard mask.

[0057] 5. The method according to any one of examples 1-4, wherein the first portion of the via has a first width of about 15 nm to about 25 nm.

[0058] 6. The method according to any one of examples 1-5, wherein the patterned hard mask layer comprises a plurality of features and each feature is separated by a second width of less than 15 nm.

[0059] 7. The method according to any one of examples 1-6, wherein the second portion of the via is disposed between two adjacent features of the plurality of features.

[0060] 8. The method according to any one of examples 1-7, wherein each of the upper metal layer, the lower metal layer, and the gapfill metal are the same.

[0061] 9. The method according to any one of examples 1-8, wherein each of the upper metal layer, the lower metal layer, and the gapfill metal comprises ruthenium, molybdenum, tungsten, alloys thereof, or any combination thereof.

[0062] 10. A method of processing a substrate, suitable for semiconductor manufacturing, comprising: depositing a low temperature oxide layer over a patterned hard mask layer, the

patterned hard mask layer comprising a plurality of openings and the low temperature oxide layer disposed within the plurality of openings; etching a first portion of a via through the low temperature oxide and through an opening within the patterned hard mask layer; etching a second portion of the via through an upper metal layer, an insulating layer, a low-k layer, and a blocking layer to expose a portion of a lower metal layer; and gap-filling the second portion of the via with a gapfill metal to connect the upper metal layer and the lower metal layer.

[0063] 11. The method according to example 10, further comprising: filling the first portion of the via with a second low temperature oxide after gap-filling the second portion; removing a portion of the low temperature oxide layer and the second low temperature oxide to form a patterned layer, wherein the low temperature oxide layer is disposed within gaps of the patterned hard mask layer; removing the patterned hard mask layer; and etching a portion of the upper metal layer through openings within the low temperature oxide layer after removing the patterned hard mask layer.

[0064] 12. The method according to example 10 or 11, wherein the insulating layer is a Tetraethyl orthosilicate layer.

[0065] 13. The method according to any one of examples 10-12, wherein the low-k layer has a dielectric constant of less than 4.

[0066] 14. The method according to any one of examples 10-13, wherein the low-k layer comprises a silicon oxycarbide.

[0067] 15. The method according to any one of examples 10-14, wherein the first portion of the via has a first width of about 15 nm to about 25 nm and the second portion of the via has a second width less than the first width and the second width is less than 15 nm.

[0068] 16. The method according to any one of examples 10-15, wherein a photoresist layer is disposed over the low temperature oxide layer and is patterned, such that etching the via is performed through a portion of the photoresist layer.

[0069] 17. The method according to any one of examples 10-16, wherein the blocking layer is an aluminum oxide layer.

[0070] 18. A layer stack disposed on a substrate, suitable for use as a semiconductor, comprising: a first metal layer; a first hard mask layer disposed on the first metal layer; one or more low-k material layers disposed over the first hard mask layer; a second metal layer disposed over the one or more low-k material layers and the first hard mask layer; a second hard mask layer disposed over the second metal layer; an oxide layer disposed over the second hard mask layer, wherein each of the second metal layer, the second hard mask layer, and the oxide layer are patterned and form a plurality of features and wherein a gapfill metal connects the first metal layer and the second metal layer and is disposed through an opening within the first hard mask and the one or more low-k material layers.

[0071] 19. The layer stack according to example 18, wherein the one or more low-k material layers comprises an insulating layer and a low-k layer.

[0072] 20. The layer stack according to example 18 or 19, wherein the gapfill metal, the first metal layer, and the second metal layer comprise the same material.

[0073] While the foregoing is directed to embodiments of the disclosure, other and further embodiments may be devised without departing from the basic scope thereof, and the scope thereof is determined by the claims that follow. All documents described herein are incorporated by reference herein, including any priority documents and/or testing procedures to the extent they are not inconsistent with this text. As is apparent from the foregoing general description and the specific embodiments, while forms of the present disclosure have been illustrated and described, various modifications can be made without departing from the spirit and scope of the present disclosure. Accordingly, it is not intended that the present disclosure be limited thereby. Likewise, the term “comprising” is considered synonymous with the term “including” for purposes of United States law. Likewise, whenever a composition, an element, or a group of elements is preceded with the transitional phrase “comprising”, it is understood that the same composition or group of

elements with transitional phrases “consisting essentially of”, “consisting of”, “selected from the group of consisting of”, or “is” preceding the recitation of the composition, element, or elements and vice versa, are contemplated. As used herein, the term “about” refers to a $\pm 10\%$ variation from the nominal value. It is to be understood that such a variation can be included in any value provided herein.

[0074] Certain embodiments and features have been described using a set of numerical upper limits and a set of numerical lower limits. It should be appreciated that ranges including the combination of any two values, e.g., the combination of any lower value with any upper value, the combination of any two lower values, and/or the combination of any two upper values are contemplated unless otherwise indicated. Certain lower limits, upper limits and ranges appear in one or more claims below.

Claims

1. A layer stack disposed on a substrate, comprising: a first metal layer; a first hard mask layer disposed on the first metal layer; one or more low-k material layers disposed over the first hard mask layer; a second metal layer disposed over the one or more low-k material layers and the first hard mask layer; a second hard mask layer disposed over the second metal layer; an oxide layer disposed over the second hard mask layer, wherein the second metal layer, the second hard mask layer, and the oxide layer are patterned and form a plurality of features; and a gapfill interconnect metal is connected to the first metal layer and the second metal layer and is disposed through the first hard mask layer and the one or more low-k material layers.
2. The layer stack of claim 1, wherein the one or more low-k material layers comprises an insulating layer and a low-k layer.
3. The layer stack of claim 2, wherein the low-k layer has a dielectric constant of less than 4.
4. The layer stack of claim 2, wherein the low-k layer comprises a silicon oxycarbide.
5. The layer stack of claim 2, wherein the insulating layer has a thickness in a range from about 3 nm to about 20 nm, and wherein the low-k layer has a thickness in a range from about 3 nm to about 20 nm.
6. The layer stack of claim 2, wherein the insulating layer comprises tetraethyl orthosilicate.
7. The layer stack of claim 1, wherein the gapfill interconnect metal was a width of less than 15 nm.
8. The layer stack of claim 1, wherein the gapfill interconnect metal was a width in a range from about 11 nm to about 20 nm.
9. The layer stack of claim 1, wherein the gapfill interconnect metal comprises ruthenium, molybdenum, tungsten, alloys thereof, or any combination thereof.
10. The layer stack of claim 1, wherein the gapfill interconnect metal, the first metal layer, and the second metal layer comprise the same material.
11. The layer stack of claim 1, wherein the first metal layer comprises ruthenium, molybdenum, tungsten, an alloy thereof, or any combination thereof.
12. The layer stack of claim 1, wherein the first metal layer has a thickness in a range from about 15 nm to about 40 nm.
13. The layer stack of claim 1, wherein the second metal layer comprises ruthenium, molybdenum, tungsten, an alloy thereof, or any combination thereof.
14. The layer stack of claim 1, wherein the second metal layer has a thickness in a range from about 15 nm to about 40 nm.
15. The layer stack of claim 1, wherein the oxide layer comprises silicon oxycarbide, silicon oxycarbonitride, boron nitride, tetraethyl orthosilicate (TEOS), dopants thereof, or any combination thereof.
16. The layer stack of claim 1, wherein the first hard mask layer comprises silicon nitride.

17. The layer stack of claim 1, wherein the first hard mask layer has a thickness in a range from about 1 nm to about 15 nm.

18. The layer stack of claim 1, wherein the second hard mask layer comprises silicon nitride.

19. The layer stack of claim 1, wherein the second hard mask layer has a thickness in a range from about 2 nm to about 20 nm.

20. A layer stack disposed on a substrate, suitable for use as a semiconductor, comprising: a first metal layer; a first hard mask layer disposed on the first metal layer; one or more low-k material layers disposed over the first hard mask layer, wherein the one or more low-k material layers comprises an insulating layer and a low-k layer, and wherein the low-k layer has a dielectric constant of less than 4; a second metal layer disposed over the one or more low-k material layers and the first hard mask layer; a second hard mask layer disposed over the second metal layer; an oxide layer disposed over the second hard mask layer, wherein the oxide layer comprises silicon oxycarbide, silicon oxycarbonitride, boron nitride, tetraethyl orthosilicate (TEOS), dopants thereof, or any combination thereof, and wherein the second metal layer, the second hard mask layer, and the oxide layer are patterned and form a plurality of features; and a gapfill interconnect metal is connected to the first metal layer and the second metal layer and is disposed through the first hard mask layer and the one or more low-k material layers.
