

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12409497
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Wakana; Tomohiro

Three-dimensional deposition device and method

Abstract

In the three-dimensional deposition device and the three-dimensional deposition method, included are: a powder passage and a nozzle injection opening serving as a powder supply unit that supplies powder toward an object to be processed; a laser path serving as a light irradiation unit that irradiates the powder with a laser beam to sinter or melt and solidify at least a part of the powder irradiated with the laser beam to form a formed layer; an interference information acquisition unit that acquires interference information on the object to be processed with the powder injected from the nozzle injection opening based on the shape of the object to be processed; and a controller that changes the powder passage of the powder that the nozzle injection opening supplies to the object to be processed based on the interference information acquired by the interference information acquisition unit.

Inventors:	Wakana; Tomohiro (Shiga, JP)
Applicant:	Mitsubishi Heavy Industries Machine Tool Co., Ltd. (Ritto, JP); Technology Research Association for Future Additive Manufacturing (Tokyo, JP)
Family ID:	73741691
Assignee:	MITSUBISHI HEAVY INDUSTRIES MACHINE TOOL CO., LTD. (Ritto, JP); TECHNOLOGY RESEARCH ASSOCIATION FOR FUTURE ADDITIVE MANUFACTURING (Tokyo, JP)
Appl. No.:	17/426521
Filed (or PCT Filed):	December 13, 2019
PCT No.:	PCT/JP2019/048861
PCT Pub. No.:	WO2020/250462
PCT Pub. Date:	December 17, 2020

Prior Publication Data

Document Identifier

US 20220097143 A1

Publication Date

Mar. 31, 2022

Foreign Application Priority Data

JP

2019-108958

Jun. 11, 2019

Publication Classification

Int. Cl.: B29C67/00 (20170101); B22F10/28 (20210101); B22F10/85 (20210101); B22F12/90 (20210101); B23K26/34 (20140101); B33Y10/00 (20150101); B33Y30/00 (20150101); B33Y50/02 (20150101)

U.S. Cl.:

CPC B22F10/85 (20210101); B22F10/28 (20210101); B22F12/90 (20210101); B23K26/34 (20130101); B33Y10/00 (20141201); B33Y30/00 (20141201); B33Y50/02 (20141201);

Field of Classification Search

CPC: B22F (10/85); B22F (10/28); B22F (12/90); B33Y (10/00); B33Y (30/00); B33Y (50/00); B33Y (50/02); B23K (26/34)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5837960	12/1997	Lewis et al.	N/A	N/A
5961862	12/1998	Lewis et al.	N/A	N/A
5993554	12/1998	Keicher et al.	N/A	N/A
6823230	12/2003	Jamalabad	700/182	G05B 19/4099
10124410	12/2017	Kanko et al.	N/A	N/A
10586630	12/2019	Yoshimura et al.	N/A	N/A
10898971	12/2020	Yoshimura	N/A	N/A
2006/0003095	12/2005	Bullen	427/256	B22F 3/004
2016/0311027	12/2015	Shimoyama	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
108580900	12/2017	CN	N/A
11-179573	12/1998	JP	N/A
2015-178192	12/2014	JP	N/A
2015-196264	12/2014	JP	N/A
I600485	12/2016	TW	N/A
I643687	12/2017	TW	N/A
WO 2016/151781	12/2015	WO	N/A

OTHER PUBLICATIONS

Extended European Search Report for European Application No. 19932681.0, dated Mar. 28, 2022, cited by applicant

Primary Examiner: Ochylski; Ryan M

Attorney, Agent or Firm: Birch, Stewart, Kolasch & Birch, LLP

Background/Summary**FIELD**

(1) The present disclose relates to a three-dimensional deposition device to manufacture a three-dimensional object by deposition and a three-dimensional deposition method.

BACKGROUND

(2) As a technique of manufacturing a three-dimensional object, there is known a deposition shaping technique of manufacturing a three-dimensional object by irradiating a metallic powder material with a light beam. As a deposition shaping technique, for example, there is a technique disclosed in Patent Literature 1. The technique disclosed in Patent Literature 1 is a technique of forming a sintered layer by irradiating a powder layer formed of a metallic powder material with a light beam and manufacturing a three-dimensional object, in which a plurality of sintered layers are integrally deposited, by repeating this process.

CITATION LIST**Patent Literature**

(3) Patent Literature 1: Japanese Patent Application Laid-open No. 2015-196264

SUMMARY**Technical Problem**

(4) In the above-described deposition shaping, a light beam is emitted from a center of a deposition head toward an object to be processed, and a metal powder material is injected from a plurality of locations around the deposition head toward a focal point of the light beam, whereby the metal powder material is heated and melted with the light beam. By the way, in a process of three-dimensional deposition work, or when three-dimensional deposition is performed on an object to be processed manufactured by machining, a working surface has an uneven shape in some cases. When the working surface has an uneven shape, part of the metal powder material injected toward the focal point of the light beam may interfere with a convex part on the working surface. Then, the metal powder material that interferes with the convex part of the working surface scatters in a path of the light beam and attenuates output of the light beam. In addition, part of the metal powder material does not reach the focal point of the light beam, that is, the object to be processed, which makes an amount of deposition of the metal powder material insufficient. This results in a problem in that quality of a three-dimensional object is degraded.

(5) The present disclosure solves the above-described problem, and aims to provide a three-dimensional deposition device and a three-dimensional deposition method for improving the quality of a three-dimensional object.

Solution to Problem

(6) To achieve the objective described above, a three-dimensional deposition device of the present disclosure is configured to form a three-dimensional object by depositing a formed layer on an object to be processed, the three-dimensional deposition device comprising: a powder supply unit

configured to supply a powder material to a working surface of the object to be processed: a light irradiation unit configured to irradiate the powder material with a light beam to sinter or melt and solidify at least a part of the powder material irradiated with the light beam to form the formed layer; an interference information acquisition unit configured to acquire interference information on the object to be processed with the powder material injected from the powder supply unit based on the shape of the object to be processed; and a controller configured to change a supply path of the powder material supplied from the powder supply unit to a working surface of the object to be processed based on the interference information acquired by the interference information acquisition unit.

(7) Therefore, the interference information acquisition unit acquires interference information on the object to be processed with the powder material injected from the powder supply unit based on the shape of the object to be processed, and the controller changes the supply path of the powder material supplied from the powder supply unit to the working surface of the object to be processed based on the interference information. In other words, the controller identifies an area where the powder material injected from the powder supply unit interferes with the object to be processed, and the powder supply unit supplies the powder material to the working surface of the object to be processed from an area where the powder material injected from the powder supply unit does not interfere with the object to be processed. As a result, the powder material does not interfere with the object to be processed and does not scatter, the output of the light beam is not attenuated, and a determined amount of powder material can be supplied to the object to be processed, whereby the quality of the three-dimensional object can be improved.

(8) In the three-dimensional deposition device of the present disclosure, the powder supply unit includes a plurality of powder injection units provided around the light irradiation unit at predetermined intervals in a circumferential direction, and the controller stops injection of the powder material from the powder injection unit injecting the powder material that is estimated to interfere with the object to be processed.

(9) Therefore, the controller stops injection of the powder material from a powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, injects the powder material from a remaining powder injection unit, and prevents scattering of the powder material occurring when the powder material interferes with the object to be processed, while it is possible to properly supply the powder material to the object to be processed, and to properly manufacture a three-dimensional object regardless of the shape of the object to be processed.

(10) In the three-dimensional deposition device of the present disclosure, when the controller stops the injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller increases an injection amount of the powder material injected from the powder injection unit other than the powder injection unit that has stopped the injection of the powder material.

(11) Therefore, when the controller stops injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller increases the injection amount of the powder material from the remaining powder injection unit, so that it is possible to constantly supply a proper amount of the powder material to the object to be processed and to prevent degradation of the quality of the three-dimensional object.

(12) In the three-dimensional deposition device of the present disclosure, when the controller stops the injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller adjusts output of the light beam emitted from the light irradiation unit.

(13) Therefore, when injection of the powder material from the powder injection unit that injects powder material that is estimated to interfere with the object to be processed stops, the output of the light beam emitted from the light irradiation unit is adjusted, so that it is possible to output a light

beam corresponding to the reduced amount of supply of the powder material and to prevent degradation of the quality of the three-dimensional object.

(14) In the three-dimensional deposition device of the present disclosure, when the controller stops the injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller adjusts the processing speed of the object to be processed.

(15) Therefore, when injection of the powder material from the powder injection unit that injects powder material that is estimated to interfere with the object to be processed stops, the processing speed of the object to be processed is adjusted, so that the processing speed becomes a processing speed corresponding to the reduced amount of supply of the powder material and it is possible to prevent degradation of the quality of the three-dimensional object.

(16) In the three-dimensional deposition device of the present disclosure, the interference information acquisition unit acquires a shape of the object to be processed in advance, an operating program of the powder supply unit and the light irradiation unit is set based on the acquired shape of the object to be processed, and the controller controls the powder supply unit or the light irradiation unit based on the operating program.

(17) Therefore, the controller controls the powder supply unit or the light irradiation unit based on the operating program of the powder supply unit and the light irradiation unit that are set based on the shape of the object to be processed, so that interference between the injected powder material and the object to be processed can be prevented regardless of the shape of the object to be processed.

(18) In the three-dimensional deposition device of the present disclosure, the interference information acquisition unit includes a detector that detects or estimates a reaching status of the powder material supplied from the powder supply unit to the object to be processed, and the controller controls the powder supply unit based on a detection result obtained by the detector.

(19) Therefore, the controller controls the powder supply unit based on the reaching status of the powder material to the object to be processed that is detected or estimated by the detector, so that interference between the injected powder material and the object to be processed can be prevented regardless of the shape of the object to be processed.

(20) The three-dimensional deposition method of the present disclosure is for forming a three-dimensional object by depositing a formed layer on an object to be processed, the three-dimensional deposition method comprising: a step of supplying a powder material toward a working surface of the object to be processed;

(21) a step of irradiating the powder material with a light beam to sinter or melt and solidify at least a part of the powder material irradiated with the light beam to form the formed layer; a step of acquiring interference information on the object to be processed with the powder material based on the shape of the object to be processed; and a step of changing a supply path of the powder material to the object to be processed based on the interference information.

(22) Therefore, the area where the powder material injected from the powder supply unit interferes with the object to be processed is identified, and the powder supply unit supplies the powder material to the working surface of the object to be processed from the area where the powder material injected from the powder supply unit does not interfere with the object to be processed. As a result, the powder material does not interfere with the object to be processed and does not scatter, the output of the light beam is not attenuated, and a determined amount of powder material can be supplied to the object to be processed, whereby the quality of the three-dimensional object can be improved.

Advantageous Effects of Invention

(23) According to the three-dimensional deposition device and the three-dimensional deposition method of the present disclosure, it is possible to improve the quality of a three-dimensional object.

Description

BRIEF DESCRIPTION OF DRAWINGS

- (1) FIG. 1 is a schematic view illustrating a three-dimensional deposition device of the present embodiment.
- (2) FIG. 2 is a longitudinal sectional view illustrating an example of a front end of a deposition head.
- (3) FIG. 3 is a horizontal sectional view illustrating an example of the front end of the deposition head.
- (4) FIG. 4 is a schematic view illustrating a configuration of a control device.
- (5) FIG. 5 is a schematic diagram illustrating a problem in manufacturing a three-dimensional object by the three-dimensional deposition device.
- (6) FIG. 6 is a time chart of a first control method of changing a supply path of a powder material by the control device.
- (7) FIG. 7 is a time chart of a second control method of changing a supply path of the powder material by the control device.
- (8) FIG. 8 is a flowchart illustrating a method of manufacturing a three-dimensional object by the three-dimensional deposition device.

DESCRIPTION OF EMBODIMENTS

(9) Hereinafter, preferred embodiments of the disclosure will be described in detail with reference to the accompanying drawings. It is noted that the disclosure is not limited to the embodiment. Then, when there are a plurality of embodiments, a combination of the embodiments may be employed.

(10) FIG. 1 is a schematic diagram illustrating a three-dimensional deposition device **1** of an embodiment. Here, in the present embodiment, one direction within a horizontal plane will be set as an X-axis direction, a direction orthogonal to the X-axis direction within the horizontal plane will be set as a Y-axis direction, and a direction (a vertical direction) orthogonal to each of the X-axis direction and the Y-axis direction will be set as a Z-axis direction.

(11) As illustrated in FIG. 1, the three-dimensional deposition device **1** is a device that manufactures a three-dimensional object on a base unit **100**. The base unit **100** is a base member on which the three-dimensional object is formed. The base unit **100** is carried to a predetermined position of the three-dimensional deposition device **1**, so that the three-dimensional object is formed on a working surface thereof. The base unit **100** of the present embodiment is a plate-shaped member. Additionally, the base unit **100** is not limited thereto. As the base unit **100**, a base member of the three-dimensional object may be used or a member adding the three-dimensional object may be used. A member corresponding to a component or a product, by forming the three-dimensional object at a predetermined position, may be used as the base unit **100**.

(12) The three-dimensional deposition device **1** includes a three-dimensional deposition chamber **2**, a spare chamber **3**, a deposition head accommodation chamber **4**, a machining unit accommodation chamber **5**, a bed **10**, a table unit **11**, a deposition head **12**, a machining unit **13**, a control device **20**, a shape measurement unit **30**, a heating head **31**, a device measurement unit **32**, a tool exchange unit **33**, a nozzle exchange unit **34**, a powder introduction unit **35**, a base movement unit **36**, an air discharge unit **37**, a gas introduction unit **38**, and a powder collection unit **39**.

(13) The three-dimensional deposition chamber **2** is a casing (a chamber) in which a part other than a designed communication part, such as a connected pipe, is sealed from the outside. It is noted that the designed communication part is provided with a valve or the like that switches a sealed state and an opened state. As required, the three-dimensional deposition chamber **2** can be in the sealed state. The three-dimensional deposition chamber **2** includes therein the bed **10**, the table unit **11**, the deposition head **12**, a part of the machining unit **13**, a part of the heating head **31**, the device

measurement unit **32**, the tool exchange unit **33**, and the nozzle exchange unit **34**.

(14) The spare chamber **3** is provided adjacent to the three-dimensional deposition chamber **2**. In the spare chamber **3**, a part other than a designed communication part, such as a connection pipe, is sealed from the outside. The spare chamber **3** is formed as a decompression chamber which connects the outside and the three-dimensional deposition chamber **2** to each other. The base movement unit **36** is provided inside the spare chamber **3**. Here, the spare chamber **3** is formed such that, for example, a door **6** having airtightness is provided at the connection part of the three-dimensional deposition chamber **2**. Furthermore, the spare chamber **3** is connected to the outside by the airtight door **7**. Furthermore, the spare chamber **3** is provided with an air discharge unit **25** that discharges air from the spare chamber **3**. When the door **7** is opened, a necessary member can be carried into the spare chamber **3** from the outside. Furthermore, when the door **6** is opened, a member can be carried between the spare chamber **3** and the three-dimensional deposition chamber **2**.

(15) The deposition head accommodation chamber **4** is provided at an upper face of the three-dimensional deposition chamber **2** in the Z-axis direction. The deposition head accommodation chamber **4** is supported by a Z-axis slide unit **4a** to be movable in the Z-axis direction (a direction of an arrow **102**) with respect to the three-dimensional deposition chamber **2**. A lower surface of the deposition head accommodation chamber **4** in the Z-axis direction is connected to the three-dimensional deposition chamber **2** by a bellows **18**. The bellows **18** connects the lower surface of the deposition head accommodation chamber **4** in the Z-axis direction to the three-dimensional deposition chamber **2**, so that the lower surface of the deposition head accommodation chamber **4** in the Z-axis direction serves as a part of the three-dimensional deposition chamber **2**. Furthermore, the three-dimensional deposition chamber **2** is formed so that an opening is formed in an area surrounded by the bellows **18**. A space surrounded by the lower surface of the deposition head accommodation chamber **4** in the Z-axis direction and the bellows **18** is connected to the three-dimensional deposition chamber **2** and is sealed along with the three-dimensional deposition chamber **2**. The deposition head accommodation chamber **4** supports the deposition head **12**, the shape measurement unit **30**, and the heating head **31**. Furthermore, a part including a nozzle **23** of the deposition head **12** and a part including a front end **24** of the heating head **31** protrude toward the three-dimensional deposition chamber **2** from the lower surface of the deposition head accommodation chamber **4** in the Z-axis direction.

(16) When the deposition head accommodation chamber **4** moves in the Z-axis direction by the Z-axis slide unit **4a**, the deposition head **12**, the shape measurement unit **30**, and the heating head **31** held therein are moved in the Z-axis direction. Furthermore, the deposition head accommodation chamber **4** is connected to the three-dimensional deposition chamber **2** through the bellows **18**, so that the bellows **18** is deformed in accordance with the movement in the Z-axis direction and the sealed state between the three-dimensional deposition chamber **2** and the deposition head accommodation chamber **4** can be maintained.

(17) The machining unit accommodation chamber **5** is provided at the upper face of the three-dimensional deposition chamber **2** in the Z-axis direction. Furthermore, the machining unit accommodation chamber **5** is disposed adjacent to the deposition head accommodation chamber **4**. The machining unit accommodation chamber **5** is supported by a Z-axis slide unit **5a** to be movable in the Z-axis direction (a direction of an arrow **104**) with respect to the three-dimensional deposition chamber **2**. A lower face of the machining unit accommodation chamber **5** in the Z-axis direction is connected to the three-dimensional deposition chamber **2** by a bellows **19**. The bellows **19** connects the lower face of the machining unit accommodation chamber **5** in the Z-axis direction to the three-dimensional deposition chamber **2** so that the lower face of the machining unit accommodation chamber **5** in the Z-axis direction is formed as a part of the three-dimensional deposition chamber **2**. Furthermore, the three-dimensional deposition chamber **2** is formed so that an opening is formed in an area surrounded by the bellows **19**. A space surrounded by the lower

face of the machining unit accommodation chamber **5** in the Z-axis direction and the bellows **19** is connected to the three-dimensional deposition chamber **2** and is sealed along with the three-dimensional deposition chamber **2**. The machining unit accommodation chamber **5** supports the machining unit **13**. Furthermore, the machining unit accommodation chamber **5** is formed so that a part including a tool **22** of the machining unit **13** protrudes toward the three-dimensional deposition chamber **2** from the lower face in the Z-axis direction.

(18) When the machining unit accommodation chamber **5** moves in the Z-axis direction by the Z-axis slide unit **5a**, the machining unit **13** held therein is moved in the Z-axis direction. Furthermore, the machining unit accommodation chamber **5** is connected to the three-dimensional deposition chamber **2** through the bellows **19**, so that the bellows **19** is deformed in accordance with the movement in the Z-axis direction and the sealed state between the three-dimensional deposition chamber **2** and the machining unit accommodation chamber **5** can be maintained.

(19) The bed **10** is provided at a bottom in the three-dimensional deposition chamber **2** in the Z-axis direction. The bed **10** supports the table unit **11**. Various wirings, pipes, or driving assemblies are disposed on the bed **10**.

(20) The table unit **11** is disposed on an upper face of the bed **10** and supports the base unit **100**. The table unit **11** includes a Y-axis slide unit **15**, an X-axis slide unit **16**, and a rotation table unit **17**. The table unit **11** has the base unit **100** attached thereto and moves the base unit **100** on the bed **10**.

(21) The Y-axis slide unit **15** moves the X-axis slide unit **16** in the Y-axis direction (a direction of an arrow **106**) with respect to the bed **10**. The X-axis slide unit **16** is fixed to a member corresponding to a movable part of the Y-axis slide unit **15**, and moves the rotation table unit **17** in the X-axis direction (a direction of an arrow **108**) with respect to the Y-axis slide unit **15**. The rotation table unit **17** is fixed to a member corresponding to a movable part of the X-axis slide unit **16** and supports the base unit **100**. The rotation table unit **17** is, for example, an inclined circular table and includes a fixing base **17a**, a rotation table **17b**, an inclination table **17c**, and a rotation table **17d**. The fixing base **17a** is fixed to a member corresponding to a movable part of the X-axis slide unit **16**. The rotation table **17b** is supported by the fixing base **17a**. The rotation table **17b** rotates about a rotation shaft **110** which is a rotation axis and is parallel to the Z-axis direction. The inclination table **17c** is supported by the rotation table **17b**. The inclination table **17c** rotates about a rotation shaft **112** which is an axis and is orthogonal to a face supporting the rotation table **17b**. The rotation table **17d** is supported by the inclination table **17c**. The rotation table **17d** rotates about a rotation shaft **114** which is an axis and is orthogonal to a surface supporting the inclination table **17c**. The rotation table **17d** fixes the base unit **100**.

(22) In this way, the rotation table unit **17** can rotate the base unit **100** about three orthogonal axes by rotating corresponding components thereof about the rotation shafts **110**, **112**, and **114**. The table unit **11** moves the base unit **100** fixed to the rotation table unit **17** in the Y-axis direction and the X-axis direction by the Y-axis slide unit **15** and the X-axis slide unit **16**. Furthermore, the table unit **11** rotates the base unit **100** about the three orthogonal axes by rotating the corresponding components thereof about the rotation shafts **110**, **112**, and **114** by the rotation table unit **17**. The table unit **11** may further move the base unit **100** in the Z-axis direction.

(23) The deposition head **12** injects a powder material toward the base unit **100**, irradiates the powder material injected onto the base unit with a laser beam (light beam) to melt the powder, and solidifies the melted powder on the base unit **100** to form a formed layer. The powder which is introduced into the deposition head **12** is powder which is used as a raw material of the three-dimensional object. In the embodiment, for example, a metal material such as iron, copper, aluminum, or titanium can be used as the powder. As the powder, a material such as ceramic other than the metal material may be used. The deposition head **12** is provided at a position facing the upper face of the bed **10** in the Z-axis direction and faces the table unit **11**. A lower part of the deposition head **12** in the Z-axis direction is provided with the nozzle **23**. The nozzle **23** is attached

to a main body **46** of the deposition head **12**.

(24) FIG. **2** is a longitudinal sectional view illustrating an example of a front end of the deposition head and FIG. **3** is a horizontal sectional view illustrating an example of the front end of the deposition head.

(25) As illustrated in FIG. **2** and FIG. **3**, the nozzle **23** is a double tube including an outer tube **41** and an inner tube **42** inserted into the outer tube **41**. The outer tube **41** is a tubular member and is formed so that a diameter decreases toward a front end (downward in the Z-axis direction). The inner tube **42** is inserted into the outer tube **41**. The inner tube **42** is also a tubular member and has a shape in which a diameter decreases toward a front end (downward in the Z-axis direction). In the nozzle **23**, powder passages (powder supply unit) **43**, through which powder (powder material) **P** passes, are formed between an inner periphery of the outer tube **41** and an outer periphery of the inner tube **42**. An inner peripheral face side of the inner tube **42** serves as a laser path (light irradiation unit) **44** through which a laser beam passes. Here, the main body **46** to which the nozzle **23** is attached is a double tube similarly to the nozzle **23** and the powder passages **43** and the laser path **44** are also formed in this way. In the deposition head **12**, the powder passages **43** are disposed to surround the periphery of the laser path **44**. In the present embodiment, the powder passages **43** serve as powder injection units that inject the powder. In the deposition head **12**, the powder **P** introduced from the powder introduction unit **35** flows through the powder passages **43** and is injected from respective nozzle injection openings (powder injection units) **45**, which are end openings between the outer tube **41** and the inner tube **42**. Furthermore, a supply amount control unit **61** is provided for each of the powder passages **43** connected to the powder introduction unit **35**.

(26) The deposition head **12** injects the powder **P** so as to have a predetermined convergence diameter at a predetermined convergence position. The convergence diameter is the diameter of a trajectory of the powder **P** when the diameter of the trajectory of the injected powder **P** is minimized. As described above, since the diameter of the nozzle **23** decreases toward the front end thereof, the deposition head **12** injects the powder **P** so as to converge inward in a radiation direction. That is, the deposition head **12** injects the powder **P** so that the trajectory of the powder **P** has a predetermined convergence diameter. Furthermore, the convergence position is a position where the trajectory of the injected powder **P** converges.

(27) The deposition head **12** is provided with a light source **47**, an optical fiber **48**, and a light concentrating unit **49**. The light source **47** outputs a laser beam. The optical fiber **48** guides a laser output from the light source **47** to the laser path **44**. The light concentrating unit **49** is disposed in the laser path **44** and is disposed in an optical path of the laser output from the optical fiber **48**. The light concentrating unit **49** concentrates a laser beam **L** output from the optical fiber **48**. The laser beam **L** which is collected by the light concentrating unit **49** is output from an end of the inner tube **42**. In the deposition head **12**, the light concentrating unit **49** is disposed in the main body **46**, but a part or the entirety of the light concentrating unit **49** may be disposed in the nozzle **23**. When a part or the entirety of the light concentrating unit **49** is disposed in the nozzle **23**, a focal position can be changed to a different position by the exchange of the nozzle **23**.

(28) The deposition head **12** is provided with the laser path **44**, through which the laser beam **L** passes, at the position of a central axis **O**, and is provided with a plurality of powder passages **43** outside the laser path **44**. Each of the powder passages **43** is provided with the supply amount control unit **61**. In the present embodiment, six powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** are provided, six nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** are provided. The six powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** are provided with supply amount control units **61a**, **61b**, **61c**, **61d**, **61e**, and **61f**, respectively. The supply amount control units **61a**, **61b**, **61c**, **61d**, **61e**, and **61f** are each configured by, for example, a device using a pump, a switching valve, or the like. The supply amount control units **61a**, **61b**, **61c**, **61d**, **61e**, and **61f** can supply the powder **P** by opening the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f**, respectively, or can stop the supply

of the powder P by closing the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f**, respectively. Moreover, the supply amount control units **61a**, **61b**, **61c**, **61d**, **61e**, and **61f** are not limited to two-stage control of opening and closing, and, for example, change the output of the respective pumps, so as to increase or decrease the introduction amount of the powder P introduced into the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** from the powder introduction unit **35**, that is, the injection amount of the powder P injected from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, enabling provision of a desired amount of powder supply. Additionally, it is preferable that the six powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** and the six nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** are provided at equal intervals in a circumferential direction; however, they may not be provided at equal intervals. Furthermore, the number of the powder passages **43** and the number of the nozzle injection openings **45** are not limited to six, and it is sufficient if they are provided in a plural number.

(29) The deposition head **12** injects the powder P from the powder passages **43** and outputs the laser beam L from the laser path **44**. The powder P injected from the deposition head **12** enters an area irradiated with the laser beam L output from the deposition head **12**, and is heated by the laser beam L at a focal point F of the laser beam L. The powder P irradiated with the laser beam L is melted and reaches the base unit **100**. The powder P that has reached the base unit **100** in a melted state is cooled and solidified. Accordingly, a formed layer is formed on the base unit **100**.

(30) Here, the deposition head **12** of the present embodiment uses the optical fiber **48** to guide the laser beam L output from the light source **47**; however, the present disclosure is not limited to using the optical fiber **48** and may use another transmission member. Furthermore, the light concentrating unit **49** may be provided in one of or both the main body **46** and the nozzle **23**. Since the deposition head **12** of the present embodiment can be processed effectively, the powder passages **43** injecting the powder P and the laser path **44** emitting the laser beam L are provided coaxially; however, the present disclosure is not limited thereto. The deposition head **12** may be formed so that an assembly for injecting the powder P and an assembly for emitting the laser beam L are provided as separate members. The deposition head **12** of the present embodiment irradiates a powder material with a laser beam, but may emit a light beam other than the laser beam as long as the powder material can be melted or sintered.

(31) As illustrated in FIG. 1, the machining unit **13** machines, for example, a formed layer or the like. The machining unit **13** is provided at a position facing the upper face of the bed **10** in the Z-axis direction and faces the table unit **11**. The tool **22** is attached to a lower portion of the machining unit **13** in the Z-axis direction. Additionally, the machining unit **13** may be provided in the movable range of the base unit **100** using the table unit **11** above the bed **10** in the Z-axis direction. Here, the arrangement position is not limited to the position of the present embodiment.

(32) FIG. 4 is a schematic diagram illustrating a configuration of the control device **20**.

(33) As illustrated in FIG. 1, the control device **20** is electrically connected to the driving units of the components (the above-described bed **10**, table unit **11**, deposition head **12**, machining unit **13**, shape measurement unit **30**, heating head **31**, device measurement unit **32**, tool exchange unit **33**, nozzle exchange unit **34**, powder introduction unit **35**, base movement unit **36**, air discharge unit **37**, gas introduction unit **38**, powder collection unit **39**, and the like) of the three-dimensional deposition device **1**, and controls the operations of the components of the three-dimensional deposition device **1**. The control device **20** is provided at the outside of the three-dimensional deposition chamber **2** or the spare chamber **3**. The control device **20** includes, as illustrated in FIG. 4, an input unit **51**, a controller **52**, a storage unit **53**, an output unit **54**, a communication unit **55**, and an interference information acquisition unit **56**. The components of the input unit **51**, the controller **52**, the storage unit **53**, the output unit **54**, the communication unit **55**, and the interference information acquisition unit **56** are electrically connected to one another.

(34) The input unit **51** is, for example, an operation panel. An operator inputs information or an instruction to the input unit **51**. The controller **52** includes, for example, a CPU (Central Processing

Unit) and a memory. The controller **52** outputs an instruction for controlling the operations of the components of the three-dimensional deposition device **1** to the components of the three-dimensional deposition device **1**. Furthermore, information and the like are input to the controller **52** from the components of the three-dimensional deposition device **1**. The storage unit **53** is, for example, a storage device such as a RAM (Random Access Memory) or a ROM (Read Only Memory). The storage unit **53** stores therein an operation program for the three-dimensional deposition device **1** controlling the operations of the components by the controller **52** executing the program, information on the three-dimensional deposition device **1**, design information on the three-dimensional object, and the like. The output unit **54** is, for example, a display. The output unit **54** displays, for example, information from the components of the three-dimensional deposition device **1**, and the like. The communication unit **55** exchanges information with, for example, a communication line such as the Internet or a LAN (Local Area Network) by communicating with the communication line. The interference information acquisition unit **56** acquires interference information on the object to be processed with the powder P injected based on the shape of the object to be processed. Additionally, it is sufficient if the control device **20** includes at least the controller **52** and the storage unit **53**. The control device **20** may output an instruction to the components of the three-dimensional deposition device **1** if the controller **52** and the storage unit **53** are provided.

(35) FIG. 5 is a schematic diagram illustrating a problem in manufacturing a three-dimensional object by the three-dimensional deposition device.

(36) As illustrated in FIG. 5, the object **90** to be processed has a first working surface **91** along a horizontal direction, a step **92** along a vertical direction, and a second working surface **93** along the horizontal direction, and thus has an uneven shaped working surface. In practice, the object **90** to be processed moves in a movement direction **M1** relative to the deposition head **12** for three-dimensional deposition, but since it is sufficient that the deposition head **12** and the object **90** to be processed move relative to each other, explanation is made herein under the presumption that the deposition head **12** moves in a processing direction **M2**. The deposition head **12** emits laser beam **L** and injects the powder P to the first working surface **91** and moves in the processing direction **M2** to perform three-dimensional deposition to form a formed layer **94**.

(37) When the deposition head **12** transitions from the three-dimensional deposition on the first working surface **91** to three-dimensional deposition on the second working surface **93**, the powder P injected on a forward side in the processing direction **M2** interferes with the step **92** and part of the second working surface **93**. Then, the powder P interfering with the step **92** and the part of the second working surface **93** scatters in the path of the laser beam **L**, and the output of the laser beam **L** is attenuated. In addition, part of the powder P does not reach the first working surface **91**, which makes the amount of deposition of the powder P (the thickness of the formed layer **94**) insufficient.

(38) In the three-dimensional deposition device **1** of the present embodiment, as illustrated in FIG. 4, the interference information acquisition unit **56** acquires interference information on the object to be processed with the powder P injected from the nozzle injection openings **45** based on the shape of the object **90** to be processed (3D CAD data, STL data, modeling tool path data, for example). The controller **52** changes, based on the interference information, the powder passages (supply path) **43** of the powder P supplied from the nozzle injection openings **45** toward the working surface of the object **90** to be processed. The interference information includes, for example, when the three-dimensional deposition is performed based on a predetermined modeling tool path, information related to the position of a nozzle injection opening **45** that supplies the powder P estimated to be blocked in the convergence path by part of the object to be processed (which may be a part that has already been deposited) and unable to converge to a predetermined position.

(39) As illustrated in FIG. 2 and FIG. 3, the deposition head **12** includes the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** at predetermined intervals in the circumferential direction around the laser path **44**, and the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** are respectively

provided to the front ends of the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f**. The controller **52** instructs the supply amount control unit **61** to stop the injection of the powder P from a nozzle injection opening, among the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, that injects the powder P that is estimated to interfere with the object **90** to be processed.

(40) At this time, as a first control method of the present embodiment, the controller **52** instructs the supply amount control unit **61** to increase the injection amount of the powder P from nozzle injection opening other than the nozzle injection opening that has stopped the injection of the powder P, among the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**. A specific control method will be described later.

(41) As a second control method of the present embodiment, the controller **52** reduces the output of the laser beam L emitted from the laser path **44** when stopping the injection of the powder P from the nozzle injection opening, among the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, that injects the powder P that is estimated to interfere with the object to be processed. At this time, the controller **52** decreases the processing speed of the object **90** to be processed. A specific control method will be described later.

(42) The interference information acquisition unit **56** acquires a shape of the object **90** to be processed (3D CAD data, STL data, modeling tool path data, for example) in advance, and an operating program for injection of the powder P and emission of the laser beam L is set based on the acquired shape of the object **90** to be processed and stored in the storage unit **53**. The controller **52** controls the injection of the powder P and the emission of the laser beam L based on the operating program stored in the storage unit **53**.

(43) In the above description, the interference information acquisition unit **56** acquires the interference information on the powder P injected from the nozzle injection openings **45** with the object to be processed based on the shape of the object **90** to be processed, but it is not limited to this configuration. For example, as the interference information acquisition unit **56**, a detector **71** may be provided that detects or estimates a reaching status of the powder P injected from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** to the object to be processed. The controller **52** controls the injection of the powder P and the emission of the laser beam L based on a detection result obtained by the detector **71** (for example, whether the powder P interferes or can interfere with the object to be processed). This detector **71** is, for example, a laser detector or a CCD camera, and is fixed to the deposition head **12** via a bracket **72**.

(44) The method of changing a supply path of the powder P by the control device **20** will now be explained. FIG. **6** is a time chart of the first control method of changing a supply path of a powder material by the control device.

(45) In a method of manufacturing a three-dimensional object by the three-dimensional deposition device **1**, as illustrated in FIG. **1**, FIG. **2**, and FIG. **3**, the present embodiment will be described using a case in which a three-dimensional object is manufactured on a first working surface **91** of the object **90** to be processed. The object **90** to be processed is, for example, a metallic plate-shaped member, but the shape and material thereof may be arbitrarily set as long as a three-dimensional object is manufactured thereon. The object **90** to be processed is mounted on the base unit **100**. The object to be processed may be part of the three-dimensional object that has already been formed by the three-dimensional deposition device **1**.

(46) The control device **20** moves the base unit **100** by the table unit **11** so that the object **90** to be processed on the base unit **100** is disposed below the deposition head **12** in the Z-axis direction. The control device **20** introduces the powder from the powder introduction unit **35** into the deposition head **12** and emits the laser beam L while injecting the powder P from the deposition head **12** along with gas. The powder P has a predetermined convergence diameter and is injected toward the object **90** to be processed on the base unit **100**. The laser beam L is emitted to the powder P with a predetermined spot diameter between the deposition head **12** and the object **90** to be processed. Here, the position of the spot diameter of the laser beam L in the Z-axis direction

with respect to the position of the convergence diameter of the powder P in the Z-axis direction and the spot diameter at the position of the convergence diameter of the powder P in the Z-axis direction can be controlled by, for example, the movement of the position of the light concentrating unit **49**.

(47) In other words, as illustrated in FIG. 2 and FIG. 5, the deposition head **12** introduces the powder P into all the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** through the operation of the supply amount control units **61a**, **61b**, **61c**, **61d**, **61e**, and **61f**, and injects the powder P from all the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, and outputs the laser beam L from the laser path **44** (time **t1** in FIG. 6). The focal point F of the laser beam L from the laser path **44** is set in the vicinity of the first working surface **91** of the object **90** to be processed, and the powder P from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** is injected toward the focal point of the laser beam L. Therefore, the powder P injected from the deposition head **12** is heated by the laser beam L at the focal point F of the laser beam L on the first working surface **91** of the object **90** to be processed. The powder P irradiated with the laser beam L is melted in the vicinity of the first working surface **91** of the object **90** to be processed, and then reaches the first working surface **91** of the object **90** to be processed. The powder P that has reached the first working surface **91** of the object **90** to be processed in the melted state is cooled and solidified. Accordingly, the formed layer **94** is formed on the first working surface **91** of the object **90** to be processed.

(48) The control device **20** irradiates the first working surface **91** of the object **90** to be processed with the laser beam L from the deposition head **12** and injects the powder P while moving the object **90** to be processed in a predetermined movement direction **M1** by the table unit **11**. Therefore, a formed layer **94** is formed which is continuous to the first working surface **91** of the object **90** to be processed. In such a case, the processing direction by the three-dimensional deposition device is **M2**. The three-dimensional deposition device **1** repeats the formation of such a formed layer **94**, thereby manufacturing a three-dimensional object in which a plurality of formed layers are integrally deposited.

(49) When the deposition head **12** shifts from three-dimensional deposition on the first working surface **91** to three-dimensional deposition on the second working surface **93**, the powder P injected on the forward side in the processing direction **M2** interferes with the step **92** and part of the second working surface **93**. The interference information acquisition unit **56** acquires the shape of the object **90** to be processed in advance, and the operating program for the timing of injection of the powder P and the timing of emission of the laser beam L is set based on the acquired shape of the object **90** to be processed and stored in the storage unit **53**. The controller **52** controls the injection of the powder P and the emission of the laser beam L based on the operating program stored in the storage unit **53** (time **t2** in FIG. 6).

(50) That is, as illustrated in FIG. 3 and FIG. 6, at time **t1**, the deposition head **12** injects the powder P from all the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, and outputs the laser beam L from the laser path **44**. Based on the shape of the object **90** to be processed that has been acquired in advance, the operating program determines that, at time **t2**, the powder P injected from the nozzle injection openings **45e** and **45f** interferes with the object **90** to be processed. Therefore, at time **t2**, while the injection of the powder P from the nozzle injection openings **45e** and **45f** is stopped, the injection amount of the powder P from the nozzle injection openings **45a**, **45b**, **45c**, and **45d** is increased. At this time, the total injection amount of the powder P injected from the nozzle injection openings **45e** and **45f** is evenly distributed and added to the injection amounts of the powder P injected from the nozzle injection openings **45a**, **45b**, **45c**, and **45d** so that the amount of the powder P injected from the deposition head **12** does not vary before and after the injection of the powder P from the nozzle injection openings **45e** and **45f** is stopped. Since there is no change in the total amount of the powder P injected at this time, the output of the laser beam L is maintained.

(51) Therefore, the injected powder P does not scatter in the path of the laser beam L, the output of

the laser beam L is not attenuated, and an insufficient amount of deposition of the powder P (the thickness of formed layer **94**) due to some powder P not reaching the first working surface **91** does not occur. Then, based on the operating program, at time **t3**, the interference between the powder P injected from the nozzle injection openings **45e** and **45f** and the processing direction M2 is released. Therefore, at time **t3**, while the injection of the powder P from the nozzle injection openings **45e** and **45f** is resumed, the injection amount of the powder P from the nozzle injection openings **45a**, **45b**, **45c**, and **45d** is reduced. Specifically, the deposition head **12** injects the same amount of the powder P from each of the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, and outputs the laser beam L from the laser path **44**.

(52) The present embodiment is not limited to the above-described control. FIG. 7 is a time chart of the second control method of changing a supply path of a powder material by the control device.

(53) As illustrated in FIG. 3 and FIG. 7, at time **t11**, the deposition head **12** injects the powder P from all the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, and outputs the laser beam L from the laser path **44**. Based on the operating program, at time **t12**, the powder P injected from the nozzle injection openings **45e** and **45f** interferes with the object **90** to be processed. Therefore, at time **t12**, the injection of the powder P from the nozzle injection openings **45e** and **45f** is stopped, and correspondingly to the reduction in the total amount of the supplied powder P, the output of the laser beam L emitted from the laser path **44** is reduced and the processing speed of the object **90** to be processed is reduced. The relation between the injection amount of the powder P, the output of the laser beam L, and the processing speed of the object **90** to be processed is confirmed in advance through an experiment or simulation, and the output of the laser beam L and the processing speed of the object **90** to be processed are set so that the thickness and the quality of the formed layer **94** will not vary.

(54) Therefore, the injected powder P does not scatter in the path of the laser beam L, the output of the laser beam L is not attenuated, variation in the amount of the deposition of the powder P (formed layer **94** thickness) due to some powder P not reaching the first working surface **91** is suppressed, and the quality is not degraded. Then, based on the operating program, at time **t13**, the interference between the powder P injected from the nozzle injection openings **45e** and **45f** and the object **90** to be processed is released. Therefore, at time **t13**, the injection of the powder P from the nozzle injection openings **45e** and **45f** is resumed, the output of the laser beam L emitted from the laser path **44** is increased, and the processing speed of the object **90** to be processed is increased. In other words, the state before time **t12** is restored.

(55) In the above description, the controller **52** is configured to control the injection of the powder P and the emission of the laser beam L based on the operating program stored in the storage unit **53**, but it is not limited to this configuration. As illustrated in FIG. 2 and FIG. 3, a configuration may be employed in which, for example, a detector **71** serving as the interference information acquisition unit **56** is provided to the deposition head **12**, which detects or estimates the reaching status of the powder P injected from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** to the object to be processed, and the injection of the powder P and the emission of the laser beam L is controlled based on the information acquired by the detector **71**. The detector **71** outputs a detection result to the controller **52** online while three-dimensional deposition is being performed using the deposition head **12**.

(56) Here, a method of manufacturing a three-dimensional object using the three-dimensional deposition device **1** will be described. FIG. 8 is a flowchart illustrating a method of manufacturing the three-dimensional object by the three-dimensional deposition device.

(57) As illustrated in FIG. 8, at step **S11**, the object **90** to be processed is mounted on the base unit **100**, and the control device **20** moves the base unit **100** by the table unit **11** so that the object **90** to be processed on the base unit **100** is disposed below the deposition head **12** in the Z-axis direction. At step **S12**, the control device **20** introduces the powder from the powder introduction unit **35** into the deposition head **12** and injects the powder P from the deposition head **12** along with the gas. At

step S13, the control device 20 emits the laser beam L. Then, at step S14, the object 90 to be processed is moved along with the base unit 100. Then, three-dimensional deposition is started at step S15 and thereafter.

(58) That is, as illustrated in FIG. 2 and FIG. 5, the deposition head 12 introduces the powder P into all the powder passages 43a, 43b, 43c, 43d, 43e, and 43f by the supply amount control units 61a, 61b, 61c, 61d, 61e, and 61f, injects the powder P from all the nozzle injection openings 45a, 45b, 45c, 45d, 45e, and 45f, and outputs the laser beam L from the laser path 44. The focal point F of the laser beam L from the laser path 44 is set in the vicinity of the first working surface 91 of the object 90 to be processed, and the powder P from the nozzle injection openings 45a, 45b, 45c, 45d, 45e, and 45f is injected toward the focal point of the laser beam L. Therefore, the powder P injected from the deposition head 12 is heated by the laser beam L at the focal point F of the laser beam L on the first working surface 91 of the object 90 to be processed. The powder P irradiated with the laser beam L is melted in the vicinity of the first working surface 91 of the object 90 to be processed, and then reaches the first working surface 91 of the object 90 to be processed. The powder P that has reached the first working surface 91 of the object 90 to be processed in the melted state is cooled and solidified. Accordingly, the formed layer 94 is formed on the first working surface 91 of the object 90 to be processed.

(59) At step S16, the control device 20 determines whether the three-dimensional deposition has ended. If it is determined that the three-dimensional deposition has not ended (No), at step S17, the controller 52 determines whether interference has occurred (or is estimated to occur) between the object 90 to be processed and the powder P injected from the nozzle injection openings 45a, 45b, 45c, 45d, 45e, and 45f based on the interference information on the object to be processed with the powder P injected from the nozzle injection openings 45, the interference information being acquired by the interference information acquiring unit 56. The interference between the powder P and the object 90 to be processed may be determined based on the shape data of the object 90 to be processed acquired by the interference information acquisition unit 56, or based on a detection result obtained by the detector 71. If it is determined that no interference has occurred (No) between the object 90 to be processed and the powder P injected from the nozzle injection openings 45a, 45b, 45c, 45d, 45e, and 45f, an injection mode of the powder P and an emission mode of the laser beam L are maintained as they are at step S18, and the process is returned to step S16 to repeat the processing. In contrast, for example, if it is determined that interference has occurred (Yes) between the object 90 to be processed and the powder P injected from the nozzle injection openings 45e and 45f among the nozzle injection openings 45a, 45b, 45c, 45d, 45e, and 45f, the injection of the powder P from the nozzle injection openings 45e and 45f is stopped, and the injection amount of the powder P from the nozzle injection openings 45a, 45b, 45c, and 45d is increased (first control method) at step S19. Alternatively, the injection of the powder P from the nozzle injection openings 45e and 45f is stopped, the output of the laser beam L emitted from the laser path 44 is reduced, and the processing speed of the object 90 to be processed is reduced (second control method).

(60) Then, the process is returned to step S16 again, and the control device 20 determines whether the three-dimensional deposition has ended. If it is determined that the three-dimensional deposition has not ended (No), the controller 52 determines at step S17 whether interference between the powder P and the object 90 to be processed has occurred. If it is determined that interference has occurred (Yes) between the powder P and the object 90 to be processed, the process is returned to step S16 via step S19, and the processing is continued. In contrast, if it is determined that the interference between the powder P and the object 90 to be processed has been released (No), the injection of the powder P from the nozzle injection openings 45e and 45f is resumed, and the injection amount of the powder P from the nozzle injection openings 45a, 45b, 45c, and 45d is reduced at step S18. In other words, the injection amount of the powder P from the nozzle injection openings 45a, 45b, 45c, 45d, 45e, and 45f is restored. Alternatively, the injection of

the powder P from the nozzle injection openings **45e** and **45f** is resumed, the output of the laser beam L emitted from the laser path **44** is increased, and the processing speed of the object **90** to be processed is increased. In other words, the injection amount of the powder P from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, the output of the laser beam L, and the processing speed of the object **90** to be processed are restored.

(61) Then, the process is returned to step **S16** again, and the control device **20** determines whether the three-dimensional deposition has ended. If it is determined that the three-dimensional deposition has ended (Yes), the control device **20** stops introduction of the powder from the powder introduction unit **35** into the deposition head **12** and stops the injection of the powder P from the deposition head **12** along with the gas at step **S20**. At step **S21**, the control device **20** stops the emission of the laser beam L. Then, at step **S22**, the control device **20** stops the movement of the object **90** to be processed along with the base unit **100**.

(62) Thus, the three-dimensional deposition device of the present embodiment includes: the powder passages **43** and the nozzle injection openings **45** serving as a powder supply unit that supplies the powder P to the processing object **90**; the laser path **44** serving as the light irradiation unit that irradiates the powder P with the laser beam L to sinter or melt and solidify at least part of the powder P irradiated with the laser beam L to form a formed layer **94**; the interference information acquisition unit **56** that acquires the interference information on the object **90** to be processed with the powder P injected from the nozzle injection opening **45** based on the shape of the object **90** to be processed; and the controller **52** that changes the powder passages **43** of the powder P supplied from the nozzle injection openings **45** toward the object **90** to be processed based on the interference information acquired by the interference information acquisition unit **56**.

(63) Therefore, the controller **52** identifies an area where the powder P injected from the nozzle injection openings **45** interferes with the object **90** to be processed, and the nozzle injection openings **45** supply the powder P to the object **90** to be processed from an area where the powder P injected from the nozzle injection openings **45** does not interfere with the object **90** to be processed. As a result, the powder P does not interfere with the object **90** to be processed and does not scatter, the output of the laser beam L is not attenuated, a determined amount of the powder P can be supplied to the object **90** to be processed, whereby the quality of a three-dimensional object can be improved.

(64) In the three-dimensional deposition device of the present embodiment, the deposition head **12** includes the powder passages **43a**, **43b**, **43c**, **43d**, **43e**, and **43f** and the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, and the controller **52** stops injection of the powder P from at least one of the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, the at least one nozzle injection opening injecting the powder P that is estimated to interfere with the object **90** to be processed. Therefore, it is possible to prevent scattering of the powder P occurring when the powder P interferes with the object **90** to be processed, while it is possible to supply the powder P to the object **90** to be processed, and to properly manufacture a three-dimensional object regardless of the shape of the object to be processed.

(65) In the three-dimensional deposition device of the present embodiment, the controller **52** increases, when stopping injection of the powder P from the at least one of the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, the at least one nozzle injection opening injecting the powder P that is estimated to interfere with the object **90** to be processed, the injection amount of the powder P from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** other than the at least one of the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, the at least one nozzle injection opening having stopped the injection of the powder P. Therefore, it is possible to constantly supply an appropriate amount of the powder P to the object **90** to be processed, and to prevent degradation of the quality of the three-dimensional object.

(66) In the three-dimensional deposition device of the present embodiment, the controller **52** adjusts, for example, decreases the output of the laser beam L emitted from the laser path **44** when

stopping the injection of the powder P from the at least one of the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, the at least one nozzle injection opening injecting the powder P that is estimated to interfere with the object **90** to be processed. Therefore, it is possible to output the laser beam L corresponding to the reduced amount of supply of the powder P, and to prevent degradation of the quality of the three-dimensional object.

(67) In the three-dimensional deposition device of the present embodiment, the controller **52** adjusts, for example, decreases the processing speed of the object **90** to be processed when stopping the injection of the powder P from the at least one of the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f**, the at least one nozzle injection opening injecting the powder P that is estimated to interfere with the object **90** to be processed. Therefore, it is possible to achieve the processing speed corresponding to the reduced amount of supply of the powder P, and to prevent degradation of the quality of the three-dimensional object.

(68) In the three-dimensional deposition device of the present embodiment, the interference information acquisition unit **56** acquires the shape of the object **90** to be processed in advance, sets the operating program for the injection of the powder P and the emission of the laser beam L based on the acquired shape of the object **90** to be processed, and the controller **52** controls the injection of the powder P and the emission of the laser beam L based on the operating program. Therefore, it is possible to prevent interference between the injected powder P and the object **90** to be processed regardless of the shape of the object **90** to be processed.

(69) In the three-dimensional deposition device of the present embodiment, as the interference information acquisition unit **56**, the detector **71** is provided to detect or estimate the reaching status of the powder P injected from the nozzle injection opening **45** to the object **90** to be processed, and the controller **52** controls the injection of the powder P based on a detection result obtained by the detector **71**. Therefore, it is possible to prevent interference between the injected powder P and the object **90** to be processed regardless of the shape of the object **90** to be processed.

(70) In addition, the three-dimensional deposition method of the present embodiment includes: a step of supplying the powder P toward the object **90** to be processed; a step of irradiating the powder P with a laser beam L to sinter or melt and solidify at least part of the powder P irradiated with the laser beam L to form the formed layer **94**; a step of acquiring interference information on the object **90** to be processed with the powder P injected from the nozzle injection openings **45** based on the shape of the object **90** to be processed; and a step of changing the powder passages **43** of the powder P supplied from the nozzle injection openings **45** to the object **90** to be processed based on the interference information.

(71) Therefore, the area where the powder P injected from the nozzle injection openings **45** interferes with the object **90** to be processed is identified, and the nozzle injection openings **45** supply the powder P to the object **90** to be processed from the area where the powder P injected from the nozzle injection openings **45** does not interfere with the object **90** to be processed. As a result, the powder P does not interfere with the object **90** to be processed and does not scatter, the output of the laser beam L is not attenuated, a determined amount of the powder P can be supplied to the object **90** to be processed, whereby the quality of a three-dimensional object can be improved.

(72) In the above-described embodiment, the interference information acquisition unit **56** is the detector **71** that detects or estimates the reaching status of the powder P injected from the nozzle injection openings **45a**, **45b**, **45c**, **45d**, **45e**, and **45f** to the object **90** to be processed, but it is not limited to this configuration. For example, the interference information acquisition unit **56** may be a CCD camera, the CCD camera may capture the shape of the object **90** to be processed, and the controller **52** may determine the interference between the powder P and the object **90** to be processed based on the shape of the object **90** to be processed.

(73) Furthermore, in the aforementioned embodiment, the powder material injected by the powder supply unit is a metallic powder material; however, a non-metallic powder material such as a resin

powder material may be used. Furthermore, the laser beam is used as a light beam; however, an electron beam and the like may be used.

REFERENCE SIGNS LIST

- (74) **1** THREE-DIMENSIONAL DEPOSITION DEVICE
- (75) **2** THREE-DIMENSIONAL DEPOSITION CHAMBER
- (76) **3** SPARE CHAMBER
- (77) **4** DEPOSITION HEAD ACCOMMODATION CHAMBER
- (78) **4a, 5a** Z-AXIS SLIDE UNIT
- (79) **5** MACHINING UNIT ACCOMMODATION CHAMBER
- (80) **6, 7** DOOR
- (81) **10** BED
- (82) **11** TABLE UNIT
- (83) **12** DEPOSITION HEAD
- (84) **13** MACHINING UNIT
- (85) **15** Y-AXIS SLIDE UNIT
- (86) **16** X-AXIS SLIDE UNIT
- (87) **17** ROTATION TABLE UNIT
- (88) **17A** FIXING BASE
- (89) **17b** ROTATION TABLE
- (90) **17c** INCLINATION TABLE
- (91) **17d** ROTATION TABLE
- (92) **18, 19** BELLOWS
- (93) **20** CONTROL DEVICE
- (94) **22** TOOL
- (95) **23** NOZZLE
- (96) **24** FRONT END
- (97) **25** AIR DISCHARGE UNIT
- (98) **30** SHAPE MEASUREMENT UNIT
- (99) **31** HEATING HEAD
- (100) **32** DEVICE MEASUREMENT UNIT
- (101) **33** TOOL EXCHANGE UNIT
- (102) **34** NOZZLE EXCHANGE UNIT
- (103) **35** POWDER INTRODUCTION UNIT
- (104) **36** BASE MOVEMENT UNIT
- (105) **37** AIR DISCHARGE UNIT
- (106) **38** GAS INTRODUCTION UNIT
- (107) **39** POWDER COLLECTION UNIT
- (108) **41** OUTER TUBE
- (109) **42** INNER TUBE
- (110) **43, 43a, 43b, 43c, 43d, 43e, and 43f** POWDER PASSAGE (POWDER SUPPLY UNIT)
- (111) **44** LASER PATH (LIGHT IRRADIATION UNIT)
- (112) **45, 45a, 45b, 45c, 45d, 45e, and 45f** NOZZLE INJECTION OPENING (POWDER INJECTION UNIT)
- (113) **46** MAIN BODY
- (114) **47** LIGHT SOURCE
- (115) **48** OPTICAL FIBER
- (116) **49** LIGHT CONCENTRATING UNIT
- (117) **51** INPUT UNIT
- (118) **52** CONTROLLER
- (119) **53** STORAGE UNIT

(120) **54** OUTPUT UNIT
(121) **55** COMMUNICATION UNIT
(122) **56** INTERFERENCE INFORMATION ACQUISITION UNIT
(123) **61, 61a, 61b, 61c, 61d, 61e, 61f** SUPPLY AMOUNT CONTROL UNIT
(124) **71** DETECTOR
(125) **72** BRACKET
(126) **90** OBJECT TO BE PROCESSED
(127) **91** FIRST WORKING SURFACE
(128) **92** STEP
(129) **93** SECOND WORKING SURFACE
(130) **94** FORMED LAYER
(131) **100** BASE UNIT
(132) **102, 104, 106, 108** ARROW
(133) **110** ROTATION SHAFT
(134) **F** FOCAL POINT
(135) **L** LASER BEAM (LIGHT BEAM)
(136) **M1** MOVEMENT DIRECTION
(137) **M2** PROCESSING DIRECTION
(138) **O** CENTRAL AXIS
(139) **P** POWDER

Claims

1. A three-dimensional deposition device configured to form a three-dimensional object by depositing a formed layer on an object to be processed, the three-dimensional deposition device comprising: a powder supply unit configured to supply a powder material to a working surface of the object to be processed; a light irradiation unit configured to irradiate the powder material with a light beam to sinter or melt and solidify at least a part of the powder material irradiated with the light beam to form the formed layer; an interference information acquisition detector configured to acquire interference information on the object to be processed with the powder material injected from the powder supply unit based on the shape of the object to be processed; and a controller configured to change a supply path of the powder material supplied from the powder supply unit to a working surface of the object to be processed based on the interference information acquired by the interference information acquisition detector, wherein the powder supply unit includes a plurality of powder injection units provided around the light irradiation unit at predetermined intervals in a circumferential direction, and the controller stops injection of the powder material from the powder injection unit injecting the powder material that is estimated to interfere with the object to be processed.
2. The three-dimensional deposition device according to claim 1, wherein, when the controller stops the injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller increases an injection amount of the powder material injected from the powder injection unit other than the powder injection unit that has stopped the injection of the powder material.
3. The three-dimensional deposition device according to claim 1, wherein, when the controller stops the injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller adjusts output of the light beam emitted from the light irradiation unit.
4. The three-dimensional deposition device according to claim 3, wherein, when the controller stops the injection of the powder material from the powder injection unit that injects the powder material that is estimated to interfere with the object to be processed, the controller adjusts the

processing speed of the object to be processed.

5. The three-dimensional deposition device according to claim 1, wherein the interference information acquisition detector acquires a shape of the object to be processed in advance, an operating program of the powder supply unit and the light irradiation unit is set based on the acquired shape of the object to be processed, and the controller controls the powder supply unit or the light irradiation unit based on the operating program.

6. The three-dimensional deposition device according to claim 1, wherein the interference information acquisition detector includes a detector that detects or estimates a reaching status of the powder material supplied from the powder supply unit to the object to be processed, and the controller controls the powder supply unit based on a detection result obtained by the detector.

7. A three-dimensional deposition method of forming a three-dimensional object by depositing a formed layer on an object to be processed, the three-dimensional deposition method comprising: a step of supplying a powder material toward a working surface of the object to be processed from a powder supply unit includes a plurality of powder injection units provided around a light irradiation unit at predetermined intervals in a circumferential direction; a step of irradiating the powder material with a light beam to sinter or melt and solidify at least a part of the powder material irradiated with the light beam to form the formed layer from the light irradiation unit; a step of acquiring interference information on the object to be processed with the powder material based on the shape of the object to be processed; and a step of changing a supply path of the powder material to the object to be processed based on the interference information, wherein in the step of changing the supply path, stopping injection of the powder material from the powder injection unit injecting the powder material that is estimated to interfere with the object to be processed.
