

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12409292
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Dunn; Jessica Lea et al.

Ultrasonic welding of fabrics for sleep apnea treatment

Abstract

A respiratory apparatus may employ ultrasonic welds. The ultrasonic welding may be used to join a variety of headgear, mask and accessory components. This process may enhance comfort, fit and/or performance of the joined components and/or overall mask assembly. A component may be a single layer component such as a textile or fabric, or a composite or multiple layer component such as fabric and foam composites, or outer fabric layers and inner spacer fabrics. Further, a component may be a strap, some other headgear component, a mask component, an accessory component or the like.

Inventors: Dunn; Jessica Lea (Scotts Head, AU), Ovzinsky; Grant Milton (Sydney, AU), Barbara; Anthony Paul (Smithfield, AU), Haskard; Kirrily Michele (Annandale, AU), Formica; Justin John (Sydney, AU), La Guzza; Michael Charles (Carlingford, AU)

Applicant: ResMed Pty Ltd (Bella Vista, AU)

Family ID: 47745767

Assignee: ResMed Pty Ltd (N/A, AU)

Appl. No.: 17/879868

Filed: August 03, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220370749 A1	Nov. 24, 2022

Related U.S. Application Data

continuation parent-doc US 16243575 20190109 US 11458271 child-doc US 17879868
continuation parent-doc US 14240167 US 10207072 20190219 WO PCT/AU2012/000981

Publication Classification

Int. Cl.: **A61M16/06** (20060101); **B29C65/00** (20060101); **B29C65/08** (20060101); **B29C65/74** (20060101); B29C65/48 (20060101); B29C65/50 (20060101); B29C65/62 (20060101); B29L31/48 (20060101)

U.S. Cl.:

CPC **A61M16/0683** (20130101); **B29C65/08** (20130101); **B29C65/7443** (20130101); **B29C66/1142** (20130101); **B29C66/14** (20130101); **B29C66/43** (20130101); **B29C66/4322** (20130101); **B29C66/4344** (20130101); **B29C66/43441** (20130101); **B29C66/436** (20130101); **B29C66/729** (20130101); **B29C66/73521** (20130101); A61M16/0633 (20140204); A61M2207/00 (20130101); B29C65/48 (20130101); B29C65/4815 (20130101); B29C65/5042 (20130101); B29C65/62 (20130101); B29C66/71 (20130101); B29C66/723 (20130101); B29C66/727 (20130101); B29L2031/4835 (20130101); F04C2270/0421 (20130101); B29C66/71 (20130101); B29K2067/00 (20130101); B29C66/71 (20130101); B29K2075/00 (20130101); B29C66/71 (20130101); B29K2077/00 (20130101)

Field of Classification Search

CPC: A61M (16/0683); A62B (18/08); A62B (9/00)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2643380	12/1952	Blair	N/A	N/A
3280406	12/1965	Immel	N/A	N/A
3819437	12/1973	Paine	N/A	N/A
3874968	12/1974	Robinson	N/A	N/A
4575874	12/1985	Johnson	2/460	A41F 15/007
5552005	12/1995	Mammino	N/A	N/A
5558556	12/1995	Froehlich	2/268	A41F 15/007
5566871	12/1995	Weintraub	224/264	A45F 3/12
6422238	12/2001	Lithgow	N/A	N/A
6625820	12/2002	Lampe	N/A	N/A
6772760	12/2003	Frater et al.	N/A	N/A
7878200	12/2010	Zollinger et al.	N/A	N/A
8136525	12/2011	Lubke et al.	N/A	N/A
9072855	12/2014	Mcauley	N/A	N/A
2007/0186931	12/2006	Zollinger et al.	N/A	N/A
2007/0261212	12/2006	Russell	N/A	N/A
2008/0034463	12/2007	Ekelund et al.	N/A	N/A
2008/0216629	12/2007	Herko	N/A	N/A
2008/0295947	12/2007	Bourbeau et al.	N/A	N/A

2009/0211583	12/2008	Carroll et al.	N/A	N/A
2010/0258132	12/2009	Moore	N/A	N/A
2010/0258136	12/2009	Doherty et al.	N/A	N/A
2011/0072553	12/2010	Ho	N/A	N/A
2011/0197341	12/2010	Formica et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1990215	12/2006	CN	N/A
100508805	12/2008	CN	N/A
2130563	12/2008	EP	N/A
3718586	12/2019	EP	N/A
2482990	12/2011	GB	N/A
100615863	12/2005	KR	N/A
2005076874	12/2004	WO	N/A
2005099801	12/2004	WO	N/A
2006130903	12/2005	WO	N/A
2009059353	12/2008	WO	N/A
2010066004	12/2009	WO	N/A
2011014931	12/2010	WO	N/A
2011022779	12/2010	WO	N/A
2012027792	12/2011	WO	N/A
2013026091	12/2012	WO	N/A

OTHER PUBLICATIONS

CN Office Action issued Apr. 13, 2020 for CN Patent Application No. 2018100325834. cited by applicant

EP Communication dated Feb. 25, 2020 for EP Application No. 17 204 178.2-1122. cited by applicant

Extended European Search Report for Application No. EP12825926 dated Jan. 29, 2015. cited by applicant

International Search Report for Application No. PCT/AU2012/000981 dated Dec. 14, 2012. cited by applicant

PCT Written Opinion for Application No. PCT/AU2012/000981 dated Dec. 14, 2012. cited by applicant

European Search Report from corresponding EP Application No. 22 166 679.5 dated Aug. 11, 2022. cited by applicant

Office Action issued in corresponding European Patent Application No. 22166679.5, mailed May 7, 2024, 6 pages. cited by applicant

Primary Examiner: Luarca; Margaret M

Attorney, Agent or Firm: Botos Churchill IP Law LLP

Background/Summary

CROSS-REFERENCE RELATED TO APPLICATION (1) The present application is a continuation of U.S. patent application Ser. No. 16/243,575, filed Jan. 9, 2019, which is a continuation of U.S. patent application Ser. No. 14/240,167, filed Feb. 21, 2014, now U.S. Pat. No.

10,207,072, which is a national phase entry under 35 U.S.C. § 371 of International Application No. PCT/AU2012/000981, filed Aug. 22, 2012, which claims priority from U.S. Provisional Patent Application No. 61/526,042, filed Aug. 22, 2011, all of which are hereby incorporated herein by reference.

FIELD OF TECHNOLOGY

(1) The present technology relates to headgear and masks, and a method of constructing them. Such masks may be suitable for use in respiratory treatment, e.g., sleep disordered breathing with continuous positive airway pressure or non-invasive positive pressure ventilation.

BACKGROUND OF TECHNOLOGY

(2) Masks used for treatment of Sleep Disordered Breathing (SDB) such as Obstructive Sleep Apnea (OSA) are typically held on a patient's head by headgear. Headgear typically includes one or more headgear straps that are adapted to engage with the mask and hold the mask in position on the patient's face.

(3) U.S. Pat. No. 6,422,238 to Lithgow discloses headgear for securing a respiratory mask having a quick release arrangement to a patient. U.S. Pat. No. 6,772,760 to Frater et al. discloses a mask system for delivering air to a user including a suspension mechanism to allow relative movement between a face-contacting cushion a mask shell. U.S. Pat. No. 8,136,525 to Lubke et al. discloses a mask system for use between a patient and a device to deliver a breathable gas to the patient, the system having a mouth cushion, a pair of nasal prongs, an elbow, and a headgear assembly. The headgear assembly provides a substantially round crown strap that cups the parietal bone and occipital bone of the patient's head during use. U.S. Pat. No. 7,878,200 to Zollinger et al. discloses a headgear for securing a patient airway interface device to a patient's head, and in particular an infant patient. The headgear includes a central body, first and second forehead straps, and first and second lower straps.

(4) Headgear and masks should be comfortable so that a patient can wear the mask at night while they sleep. There is a continuous need in the art for headgear and masks that are comfortable, fit a wide range of patients, are easily manufactured, and are inexpensive.

SUMMARY OF TECHNOLOGY

(5) A first aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding components in a manner that enhances comfort, fit and/or performance.

(6) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding at least first and second headgear components to create a flush joint.

(7) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding at least first and second headgear components in a manner that locates ultrasonic welding joints to create a flush joint. The flush joint may be adapted to connect the first and second headgear components without substantially increasing the thickness of the headgear i.e. the thickness of the headgear is the greater of the thicknesses of the first and second headgear components and not the sum of the thicknesses of the first and second headgear components.

(8) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding at least first and second headgear components in a manner that locates ultrasonic welding joints to create a flush joint. The flush joint may be reinforced. The overall thickness of the joint may be equal to the thickness of the greater one of the first and second components, plus the thickness of the reinforcing.

(9) Another aspect of the disclosed technology relates to a method of making headgear comprising joining at least first and second headgear components to create a flush joint. The method of joining the at least first and second headgear components may include heat embossing, or using lasers (such as CO.sub.2 lasers), hot air, or a heated plate or knife.

(10) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding at least first and second headgear components in a manner that locates

ultrasonic welding joints to allow or disallow flexibility in at least one portion of the combined components.

(11) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding a substantially flat first headgear component to a curved second headgear component, wherein the curved second headgear component is attached at an edge portion of the flat first headgear component to provide a rounded surface at the area of patient contact to increase comfort for the patient.

(12) Another aspect of the present technology relates to a method of making headgear comprising ultrasonically welding a first fabric having a first stiffness to a second fabric having a second stiffness, wherein the first fabric is wider than the second fabric and the first stiffness is greater than the second stiffness.

(13) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding together a strap and a fastening member such that a portion of the strap is removed and the fastening member is nested within the portion of the strap in a recessed manner.

(14) Another aspect of the disclosed technology relates to a method of making headgear comprising ultrasonically welding together a more rigid, less flexible member and a more flexible, less rigid member in an alternating manner to allow or disallow flexibility in at least one portion of the headgear.

(15) Another aspect of the disclosed technology relates to a method of making headgear for use in holding a respiratory mask in position on a patient's face. The method comprises forming at least first and second headgear components each including at least a fabric material, overlapping the at least first and second headgear components in an ultrasonic welding tool, removing an overlapping portion from at least one of the first and second headgear components, and in the 'cut and seal' process described, ultrasonically welding together the at least first and second headgear components to form an ultrasonic welding joint, thereby forming at least one headgear section. The resulting ultrasonic 'butt' or 'flush' joint may then be reinforced by means of any one or more of stitching, tacking, overmoulding with a polymer, spot welding, applying a thin fabric with an adhesive backing, applying hot-melt seam tape, and/or other method of reinforcement.

(16) Another aspect of the disclosed technology relates to a method of making a comfort pad for use with headgear in holding a respiratory mask in position on a patient's face. The method comprises ultrasonically welding a padded member to a first substantially flat member thereby forming a first ultrasonic welding joint, wherein the padded member is arranged to provide a cushion between the patient and the headgear, and the first flat member is arranged to overwrap the headgear to position the padded member on the patient's face.

(17) Another aspect of the disclosed technology relates to a method of forming a mask assembly for use in treating a patient for sleep disordered breathing. The method comprises ultrasonically welding a first component to a second component thereby forming at least a first mask section, wherein first mask section at least partially forms a cavity that delivers pressurized air to the patient. The resulting ultrasonic 'butt' or 'flush' joint may then be reinforced by means of stitching, tacking, overmoulding with a polymer, spot welding, applying a thin fabric with an adhesive backing, applying hot-melt seam tape, and/or other method of reinforcement.

(18) Another aspect of the disclosed technology relates to a mask assembly for use in treating a patient for sleep disordered breathing. The mask assembly comprises a first component, a second component, and an ultrasonic welding joint which may be overlapped, or flush joined, or reinforced, interconnecting the first component and the second component by way of creating an overlap or a flush weld thereby forming at least a first mask section, wherein the first mask section at least partially forms a cavity that delivers pressurized air to the patient.

(19) Another aspect of the disclosed technology relates to a headgear for use in supporting a respiratory mask in position on a patient's face for positive pressure treatment of the patient. The headgear comprises a first headgear component and a second headgear component, wherein the

first and second headgear components include at least a fabric material which may be laminated to a membrane or foam layer, or have multiple layers, or comprised of a three-dimensional spacer fabric construction, or could be of a knitted, woven or non-woven construction. An ultrasonic welding joint interconnects the first headgear component and the second headgear component thereby forming at least a first headgear section, wherein a space is formed between the first and second headgear components.

(20) Another aspect of the disclosed technology relates to a method of making headgear for use in holding a respiratory mask in position on a patient's face. The method comprises ultrasonically welding a first headgear component to a second headgear component thereby forming at least a first headgear section having a space situated between the first headgear component and the second headgear component, the first and second headgear components including at least a fabric material.

(21) Another aspect of the disclosed technology relates to a headgear for use in supporting a respiratory mask in position on a patient's face for positive pressure treatment of the patient. The headgear comprises a first headgear component formed of a first fabric and a second headgear component formed of a second fabric, wherein the second fabric is softer than the first fabric. An ultrasonic welding joint interconnects the first headgear component and the second headgear component thereby forming at least a first headgear section, wherein the first and second headgear components are connected to one another such that the second headgear component covers a portion of the first headgear component.

(22) Another aspect of the disclosed technology relates to a method of making headgear for use in holding a respiratory mask in position on a patient's face. The method comprises nesting first headgear components in at least one sheet of material, nesting second headgear components in the at least one sheet of material, cutting the first and second headgear components from the at least one sheet of material, and ultrasonically welding the first headgear components and the second headgear components to form at least one headgear.

(23) Another aspect of the disclosed technology relates to headgear for use in supporting a respiratory mask in position on a patient's face for positive pressure treatment of the patient. The headgear comprises a first strap having a first vector, a second strap having a second vector different from the first vector, and an ultrasonic welding joint interconnecting the first strap and the second strap thereby forming at least a first headgear section. To prevent the joint from tearing or delaminating, it may be reinforced by means of stitching, tacking, overmoulding with a polymer, spot welding, applying a thin fabric with an adhesive backing, applying hot-melt seam tape, or other method of reinforcement.

(24) Another aspect of the disclosed technology relates to headgear for use in supporting a respiratory mask in position on a patient's face for positive pressure treatment of the patient. The headgear comprises a substantially flat member including at least a fabric material and a curved member joined to the flat member by ultrasonic welding thereby forming a seamless joint, wherein the curved member is attached at an edge portion of the flat member to provide a rounded surface to increase comfort for the patient.

(25) While the above aspects are described in relation to methods or headgear being made in part by ultrasonic welding, it is noted that such ultrasonic welding is not necessary, as alternative joining techniques may be used.

(26) Other aspects, features, and advantages of this technology will become apparent from the following detailed description when taken in conjunction with the accompanying drawings, which are a part of this disclosure and which illustrate, by way of example, principles of this technology.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The accompanying drawings facilitate an understanding of the various embodiments of this technology. In such drawings:
- (2) FIGS. 1-1 to 1-5 illustrate a process of joining components by ultrasonic welding according to an example of the disclosed technology;
- (3) FIG. 2-1 is a perspective view of headgear according to an example of the disclosed technology;
- (4) FIG. 2-2 is a perspective view of headgear similar to that shown in FIG. 2-1 having a straight profile along a lower join line;
- (5) FIG. 3-1 is a top view of headgear in a partially assembled state according to an example of the disclosed technology;
- (6) FIG. 3-2 is an enlarged detail from FIG. 3-1 showing an overlapping region of headgear components according to an example of the disclosed technology;
- (7) FIG. 3-3 is enlarged detail from FIG. 3-1 showing another overlapping region of headgear components according to an example of the disclosed technology;
- (8) FIG. 3-4 illustrates the shape of a sonotrode or anvil for ultrasonically welding the overlapping region of FIG. 3-3 according to an example of the disclosed technology;
- (9) FIG. 3-5 illustrates the shape of a sonotrode or anvil for ultrasonically welding the overlapping region of FIG. 3-2 according to an example of the disclosed technology;
- (10) FIGS. 3-6 and 3-7 show headgear components nested in a sheet of material according to an example of the disclosed technology;
- (11) FIG. 3-8 shows a top strap of the headgear of FIG. 3-1 according to an example of the disclosed technology;
- (12) FIG. 3-9 shows a bottom strap of the headgear of FIG. 3-1 according to an example of the disclosed technology;
- (13) FIG. 4-1 is a top view of a headgear section including three components joined by ultrasonic welding according to an example of the disclosed technology;
- (14) FIG. 4-2 is a cross-sectional view along the line A-A of FIG. 4-1;
- (15) FIG. 4-3 is a cross-sectional view of another example of a headgear section along a line similar to line A-A of FIG. 4-1;
- (16) FIGS. 4-4 and 4-5 are cross-sectional views of headgear having a spacer fabric cushion layer;
- (17) FIG. 4-6 is an alternative configuration of a headgear section having three components joined by ultrasonic welding according to another example of the disclosed technology;
- (18) FIG. 4-7 is a cross-sectional view of headgear components welded together and reinforced with seam reinforcing tape;
- (19) FIG. 4-8 is an alternative configuration of a headgear section having three components and seam tape for flexibility joined by ultrasonic welding according to another example of the disclosed technology;
- (20) FIG. 5 is a top view of a headgear section including a plurality of straps joined by ultrasonic welding according to an example of the disclosed technology;
- (21) FIG. 6 is a top view of a headgear section including a plurality of components joined by ultrasonic welding according to an example of the disclosed technology;
- (22) FIG. 7-1 illustrates a headgear section including a rounded edge according to an example of the disclosed technology;
- (23) FIG. 7-2 is a side view of the headgear section of FIG. 7-1;
- (24) FIG. 8-1 is a partial perspective view of a strap including hook material ultrasonically joined to the strap according to an example of the disclosed technology;
- (25) FIG. 8-2 is a cross-sectional view along the line B-B of FIG. 8-1;
- (26) FIG. 9 is a partial perspective view of a component including a more rigid less flexible

member and a more flexible less rigid member joined by ultrasonic welding according to an example of the disclosed technology;

(27) FIG. 10-1 is a perspective view of a comfort pad having sections joined by ultrasonic welding according to an example of the disclosed technology;

(28) FIG. 10-2 is a side view of the comfort pad of FIG. 10-1;

(29) FIG. 11-1 is a side view of a comfort pad according to another example of the disclosed technology;

(30) FIG. 11-2 is a side view of the comfort pad of FIG. 11-1 attached to a headgear strap according to an example of the disclosed technology;

(31) FIG. 11-3 is a top view of the comfort pad of FIG. 11-1;

(32) FIGS. 12-1 to 12-5 illustrate a method of forming a mask assembly utilizing ultrasonic welding according to an example of the disclosed technology;

(33) FIG. 13-1 illustrates a process of ultrasonically welding two components to form a space between the components according to an example of the disclosed technology;

(34) FIG. 13-2 is a side view of a headgear section including a pocket and a rigidizer to be disposed in the pocket according to an example of the disclosed technology;

(35) FIG. 13-3 is a front view of a headgear section including a rigidizer according to an example of the disclosed technology;

(36) FIG. 13-4 is a front view of two components ultrasonically welded to form a space therebetween;

(37) FIGS. 13-5 and 13-6 illustrate a curved profile strap with a rounded edge profile near the patient side in the relaxed condition and the compressed condition, respectively;

(38) FIG. 14 is a partial perspective view of a component ultrasonically welded to a strap to form a strap tidy according to an example of the disclosed technology;

(39) FIG. 15-1 is a side view of a softer component ultrasonically welded to another component to form a softer patient interface according to an example of the disclosed technology;

(40) FIG. 16-1 is a top view of a headgear section including a plurality of components ultrasonically welded according to an example of the disclosed technology; and

(41) FIG. 16-2 illustrates a process of nesting headgear components in a sheet of material to increase yield.

DETAILED DESCRIPTION OF ILLUSTRATED EXAMPLES

(42) The following description is provided in relation to several examples which may share common characteristics and features. It is to be understood that one or more features of any one example may be combinable with one or more features of the other examples. In addition, any single feature or combination of features in any of the examples may constitute an additional example or examples.

(43) In this specification, the word “comprising” is to be understood in its “open” sense, that is, in the sense of “including”, and thus not limited to its “closed” sense, that is the sense of “consisting only of”. A corresponding meaning is to be attributed to the corresponding words “comprise”, “comprised” and “comprises” where they appear.

(44) 1. Headgear

(45) Some of the figures illustrate headgear according to examples of the disclosed technology. In the illustrated examples, headgear is adapted to be removably attached to a mask to hold and maintain the mask in a desired position on a patient's face. While headgear may be illustrated independently and unassociated with a mask used for treatment of SDB (e.g., by pneumatically splinting the patient's airways with gas pressurized in the range of about 2-30 cm H.sub.2O (typically 8-12 cm H.sub.2O)), it should be appreciated that each headgear may be adapted for use with any suitable mask such as, for example, full-face mask, nasal mask, mouth mask, nozzles or puffs, nasal prongs and the like, with any suitable configuration (e.g., with or without forehead support).

(46) Also, it should be appreciated that the headgear may be used with a new mask or the headgear may be retrofit to an existing mask.

(47) 2. Ultrasonic Welding Process

(48) Ultrasonic welding may be used to join a variety of headgear, mask and accessory components. This process may enhance comfort, fit and/or performance of the joined components and/or associated devices. A component may be a single layer component such as, for example, textile and fabric or a composite or multiple layer component (e.g., fabric and foam composite, coated fabric, a fabric and membrane laminate, or outer fabric layers with an inner spacer fabric). Further, a component may be a strap, some other headgear component, a mask component, an accessory component, etc.

(49) FIGS. **1-1** to **1-5** illustrate a method of joining components by ultrasonic welding according to an example of the disclosed technology. Components may be joined along their length (as shown in FIGS. **1-1** to **1-5**), or may be stacked and ultrasonically welded one on top of the other as will be described later.

(50) FIG. **1-1** illustrates a first component **102** and a second component **104** which are overlapped and placed in an ultrasonic welding tool **110**, as shown in FIGS. **1-2** and **1-3**. As seen in FIG. **1-3**, the ultrasonic welding tool **110** includes a sonotrode **112** and a knife plate **114**. The sonotrode **112** produces ultrasonic vibration that welds the components **102**, **104** as one skilled in the art will understand. The vibration of the sonotrode **112** may create energy which may then be converted into heat energy by an anvil. The anvil may be a perimeter knife line **116** on knife plate **114** as shown in FIG. **1-4**. The knife line **116** may then cut and seal a component, the cutting achieved by the sharp edge and the sealing achieved by the heat. The knife line **116** may be a single line of sharp edge or may be a series of small sharp edges (e.g. for spot welding). The knife plate is pre-shaped with a knife line in accordance with a desired shape to be cut from the components **102**, **104**. Thus, as the knife plate acts against the sonotrode, first component waste **132** and second component waste **134** are removed in a single cut and seal operation, resulting in a single component combination **122**, as shown in FIG. **1-5**. The knife plate **114** and the sonotrode **112** ultrasonically weld the first and second components thereby forming a joint **124** that connects the first component **102** and the second component **104**. The knife plate **114** also shapes the components **102**, **104** (simultaneously as it formed the joint **124**), and in this example, shapes components **102**, **104** into headgear straps. As mentioned earlier, an advantage of this process is that the components **102**, **104** can be overlapped in the ultrasonic welding tool **110** with no need to align the edges of the components. The ultrasonic welding tool **110** removes the overlapping second component waste **134** and joins the components such that the resulting combination has a constant or uniform thickness—hence the term ‘flush joint’ as the components joined together are flush or in line with one another rather than there being added thickness. It should be noted that more than two components may be ultrasonically welded in this manner. The resulting ultrasonic ‘butt’ or ‘flush’ joint may then be reinforced by any one or more of means of stitching, tacking, overmoulding with a polymer, spot welding, applying a thin fabric with an adhesive backing, applying hot-melt seam tape, and/or other method of reinforcement.

(51) 2. Ultrasonic Welding Joint

(52) The ultrasonic welding process may be arranged to provide a joint of the connected components, such as a flush joint. When stitching two components together, the components must be overlapped, and hence the final thickness of the stitched portion is the thickness of the two components added together. Unlike stitching, ultrasonically welded components may be overlapped in the tool and then welded, which results in a melted portion at the point contact between the components that are welded. The melted portion forms a joint that connects the components. The portion of the first component that was overlapped onto the second component may be discarded so the remaining portion of the first component abuts the second component and forms a flush or abutting joint. The thickness of the joint may be no thicker than the thickness of the first or second

component or may be less than both combined. This is best shown in FIG. 1-5, where the second component waste **134** was the overlapping portion and is subsequently discarded, and the first component **102** and a second component **104** abut one another at joint **124** to form a single component combination **122** in a flush, homogenous, and/or flat manner.

(53) An advantage of the ultrasonic welding process is that a flush or butt joint does not increase the thickness of the components at the joint and is visually appealing, unlike stitching where components must be overlapped and which results in an uneven thickness. Even if the edges of the two or more components are butted together and stitched without any or substantial overlapping, the stitches will create a rougher, stiffened and raised joint. Further, the ultrasonic flush or butt joint may result in a smooth connection that may reduce skin irritation, chaffing or facial marking, even when reinforced with seam reinforcement tape. An advantage of using an overlapped ultrasonic weld variation is that multiple components may be joined in a single machine in one operation. Another advantage of ultrasonic welding is that multiple components may be situated in the ultrasonic welding machine in an overlapping manner without aligning the edges of the components, as the edges of the joint will be neatened during the cut and sealing process and the excess material may be removed.

(54) Furthermore, the ultrasonic welding process may be designed such that the joint is embodied as a thinned region or thinned portion between the components. The thinned region may function as a flex point or hinge (e.g., a living hinge) to provide increased flexibility where desired. The flex point or hinge may be reinforced using hot-melt seam tape, or a thinner fabric layer with an adhesive backing, or other reinforcement methods.

(55) 3. Ultrasonic Welding Along Component Length

(56) Components may be joined along their length to create a single component (e.g., straps joined to form headgear).

(57) In an example of the disclosed technology, headgear **200**, shown in FIG. 2-1, may be formed by ultrasonically welding various components. Headgear **200** includes two lateral crown sections **210** and an upper crown section **212** forming a ring-like shape configured to fit the crown of a patient's head. Top straps **204** and bottom straps **206** depend from the crown section and are adapted to hold a mask in place on a patient's face. The top straps **204** may include adjustment members **205** (e.g., hook material) for securing the straps. Similarly, the bottom straps **206** may include adjustment members **207** (e.g., hook material). The lateral crown section **210**, the upper crown section **212**, the top straps **204** and the bottom straps **206** may be ultrasonically welded resulting in joints **222**, **224**, **236**, **238**. The joint **222** may interconnect the top strap **204** and both the upper crown section **212** and the lateral crown section **210**. The joint **224** may interconnect the lateral crown section **210** and the upper crown section **212**. The bottom straps **206** may be connected such that the joint **238** interconnects the bottom straps. The joint **236** may interconnect the lateral crown section **210** and the bottom straps **206**. Accordingly, as illustrated the headgear may be formed with welded tri-joints such as in the case of joints **222**, **224** where three components abut. Similarly, welded bi-joints may be formed as in the case of joint **238**. Of course, additional joints may be created (e.g., quad-joints, etc.).

(58) As mentioned earlier, the joints **222**, **224**, **236**, **238** may be constructed as a thinned region to encourage bending. Such a hinge feature may permit the headgear to better accommodate the shape of a patient's head. The joint **238** may provide a more flexible region as compared to the curved joint **236**, since the joint **238** extends substantially linearly thereby providing a linear axis about which the bottom straps **206** may pivot. The joint **236** extends in a nonlinear or curved manner which may provide a lower level of flexibility. The curvature in the joint **236** may also determine the direction of flexion. For ease of manufacturability, the join line **236** might be substantially straight, as shown in FIG. 2-2. A combination of linear and nonlinear joints, such as at the connection of the lateral crown section **210**, the upper crown section **212** and the top straps **204**, may be utilized to achieve a desired level of flexibility and direction of flexion, as well as a desired

level of three-dimensional shaping to a component made up of a series of parts which were originally a flat material (such as fabric or paper, for example). Such shaping may include darts, tucks, gathers, or a curved seam.

(59) Referring to FIG. 3-1, in another example of the disclosed technology, headgear **300** may be formed by ultrasonically welding various components. Headgear **300** is similar to headgear **200** described above and includes a crown section formed of two lateral crown sections **310** and an upper crown section **312**. The top straps **304** include adjustment members **305** (e.g., hook material) and bottom straps **306** include adjustment members **307** (e.g., hook material). The top and bottom straps **304**, **306** may also include unbroken loop material on an outer surface to cooperate with the adjustment members.

(60) The lateral crown sections **310**, the upper crown section **312**, the top straps **304** and the bottom straps **306** may be made of a spandex or elastane/foam composite, or could be formed of other suitable materials (such as a 3D spacer fabric or a double-knit interlock fabric). These components may be cut from a sheet of material (e.g., flame laminated), or cut from a roll of narrow fabric strap and then thermoformed and ultrasonically welded to create rounded edges before being ultrasonically welded together. The components may have a geometry that allows them to be nested on the sheet to increase yield e.g. the geometry may be substantially linear.

(61) FIG. 3-2 is an enlarged detail from FIG. 3-1 showing an overlapping region **324** of the lateral crown section **310**, the upper crown section **312** and an upper strap **304**. Specifically, as seen in FIG. 3-2, portions of upper crown section **312** and the upper strap **304** overlap and portions of the lateral crown section **310** and upper strap **304** also overlap as shown by the shaded regions. These members may be placed in an ultrasonic welding tool **110**, as described above, for ultrasonic welding. The ultrasonic welding tool **110** may weld together overlapping portions by applying ultrasonic vibrations to the anvil **324** in order to join the overlapping components of the lateral crown section **310**, the upper crown section **312** and an upper strap **304** in one process and may form an overlapped tri-joint. Similarly, referring to FIG. 3-3, the ultrasonic welding tool will join an edge of the lateral crown section **310** and an edge of the bottom strap **306** at the overlapping region **326** and may form an overlapped bi-joint.

(62) The joints in the headgear **300** may be arranged to provide flexibility or areas of rigidity in the same manner as described above with regard to the headgear **200**.

(63) Referring to the anvil tool shown in FIG. 3-4, adapted to create overlapping region **326**, in an example, D1 may be about 11.7-17.7 mm, e.g., 14.7 mm, D2 may be about 10.9-16.9 mm, e.g., 13.9 mm, D3 may be about 18.15-28.15 mm, e.g., 23.15 mm, D4 may be about 7-11 mm, e.g., 9.0 mm, D5 may be about 2.5-5.5 mm, e.g., 4.0 mm, D6 may be about 1.2-2.0 mm, e.g., 1.6 mm, the radius of curvature R1 may be about 74.6-114.6 mm, e.g., 94.6 mm, the radius of curvature R2 may be about 0.8-1.2 mm, e.g., 1.0 mm, the radius of curvature R3 may be about 70-110 mm, e.g., 90 mm, the radius of curvature R4 may be about 2.3-3.7 mm, e.g., 3.0 mm, the radius of curvature R5 may be about 3.1-4.9 mm, e.g., 4.0 mm, and the radius of curvature R6 may be about 1.9-3.1 mm, e.g., 2.5 mm.

(64) Referring to the anvil tool shown in FIG. 3-5, adapted to create overlapping region **324**, in an example, D1 may be about 7.15-12.15 mm, e.g., 9.65 mm, D2 may be about 10.75-16.75 mm, e.g., 13.75 mm, D3 may be about 23.55-37.55 mm, e.g., 30.55, D4 may be about 3.75-6.25 mm, e.g., 5.0 mm, the radius of curvature R1 may be about 1.25-2.75 mm, e.g., 2.0 mm, and the angle $\alpha 1$ may be about 20.0-40.0°, e.g., 30°.

(65) The area of the anvil tools described in FIG. 3-4 and FIG. 3-5 may be patterned with a series of raised areas (such as squares, or dots, or diamonds) which may function to focus the energy of the vibrating ultrasonic sonotrode, thus generating heat at the tip of these raised areas, this heat then melts the material of the components being joined, thus fusing the parts together.

(66) FIG. 3-6 illustrates lateral crown sections **310** situated on a sheet of material from which they are cut. The lateral crown sections **310** are arranged on the sheet to maximize yield. In an example,

D1 may be about 99.43-179.43 mm, e.g., 139.43 mm, D2 may be about 58.8-98.8 mm, e.g., 78.8 mm, and D3 may be about 30.0-50.0 mm, e.g., 40.0 mm.

(67) FIG. 3-7 illustrates upper crown sections **312** situated on a sheet of material from which they are cut. The upper crown sections **312** are arranged on the sheet to maximize yield. In an example, D1 may be about 157.97-257.97 mm, e.g., 207.97 mm, D2 may be about 27.43-47.43 mm, e.g., 37.43 mm, and D3 may be about 20.0-40.0 mm, e.g., 30.0 mm.

(68) FIG. 3-8 illustrates top straps **304** situated on a sheet of material from which they are cut. The top straps **304** are also arranged on the sheet to maximize yield. In an example, D1 may be about 187-287 mm, e.g., 237 mm, D2 may be about 14-22 mm, e.g., 18 mm, D3 may be about 20-36 mm, e.g., 28 mm, and D4 may be about 17.28-27.28 mm, e.g., 22.28 mm.

(69) FIG. 3-9 illustrates bottom straps **306** situated in on a sheet of material from which they are cut. Similarly, the bottom straps **306** are arranged on the sheet to maximize yield. In an example, D1 may be about 232-372 mm, e.g., 302 mm, D2 may be about 14-22 mm, e.g., 18 mm, and D3 may be about 20-36 mm, e.g., 28 mm.

(70) 3.1 Examples

(71) In the following sections, further techniques, arrangements and/or benefits of ultrasonic welding according to examples of the disclosed technology are described. Such techniques and/or arrangements may enhance comfort, fit and/or performance of headgear, masks and/or accessories. It is noted that any feature described, above or below, in relation to headgear may also be usable with a mask and/or accessory item, and vice versa.

(72) 3.1.1 Even Surfaces at Join

(73) Headgear **400** includes a first headgear component **402**, a second headgear component **404** and a third headgear component **406**, as shown in FIGS. 4-1 and 4-2. The headgear components may be straps. The headgear components **402**, **404**, **406** are joined by ultrasonic welding at a point where all three components meet, in a cut and seal process that creates a butt joint or welded butt tri-joint (i.e. joint of three components).

(74) As shown in FIG. 4-2, the first headgear component **402** may include an outer textile **402-1**, an inner textile **402-2** and a cushion layer (e.g., foam or 3D spacer fabric) **402-3**. The second headgear component **404** may include an outer textile **404-1**, an inner textile **404-2** and a cushion layer (e.g., foam or spacing filaments) **404-3**.

(75) As illustrated in FIG. 4-2, the ultrasonic welding process results in a joint **410** that interconnects the first and second headgear components **402**, **404** and permits top (**402-1**, **404-1**) and bottom (**402-2**, **404-2**) surfaces of the components to be aligned thereby providing a smooth, even butt joint which enhances patient comfort. In the alternative, a stitched butt joint would result in the first and second components **402**, **404** being connected with a raised area of thread (e.g., sewn with a zig-zag stitch) which provides an uneven, rough surface that may be uncomfortable to the patient. Alternatively, a flat lap seam that covers the raw edges of the fabric could be stitched here; this structure may be less desirable especially when used with cushioned fabrics as a flat lap seam is not truly flat, rather it consists of four fabric layers due to a folding and interlocking process. An exemplary lap seam can be seen in GB 2482990, which is hereby incorporated by reference in its entirety. While it is neat, the seam creates a thicker surface (i.e. thickness of the joint is greater than the thickness of the materials) which may cause patient discomfort, therefore a butt or simple overlap ultrasonic seam or weld is most desirable.

(76) Referring to FIG. 4-3, even if the first and second components **402**, **404** have a different thickness, in the case of a thicker crown strap being ultrasonically welded to a front strap, the inner textile layers or patient interface surfaces **402-2**, **404-2** may be aligned to provide a smooth, even patient interface. That is, the patient side surface of the joined components may be welded so that these surfaces are flush, while the opposing surfaces are not flush.

(77) An alternative example is shown in FIG. 4-4 which illustrates a first headgear component **402** that includes an outer textile **402-1**, an inner textile **402-2** and a spacer fabric cushion layer **402-4**

and a second headgear component **404** includes an outer textile **404-1**, an inner textile **404-2** and a spacer fabric cushion layer **404-4**. FIG. 4-5 illustrates this configuration using components of different thicknesses, D1 and D2, similar to that shown for FIG. 4-3.

(78) Additionally, headgear **400** may be configured with bi-joints shown in FIG. 4-6 to include a first headgear component **402** and a third headgear component **406** joined to two ends of a second head gear component **404** instead of meeting a triple point as shown in FIG. 4-1 as a tri-joint. As seen in FIG. 4-6, the first headgear component **402** and the third headgear component **406** do not directly contact one another and are instead joined to second headgear component **404**.

(79) As shown in FIG. 4-7, in at least some examples, the resulting butt weld joint **410** between two components **402**, **404** may be reinforced with seam tape. One way of reinforcing the weld while maintaining the low profile flush surface is to laminate or cover it with a tape **420** formed of a thermoplastic film or sheet. In some examples, tape **420** is formed of a seam reinforcing tape such as Sewfree® tapes provided by Bemis. The tape may serve to reinforce seams created by ultrasonic or laser equipment. The ultrasonically bonded seam may require additional strength and may not be not be entirely waterproof. Reinforcing tapes may be applied to the seams to create superior seam strength and further weatherproof the joint without adding significant bulk. In some examples, the tape may have a thickness of between about 0.1 mm and about 1 mm. The tape may also be formed of multi-layered thermoplastic adhesive film or from coated fabrics. In this manner, tapes may be applied to the joint to prevent water from soaking through the joint and may be applied by using a hot air taping machine. Tape **420** may also be formed of heat seal seam tape.

(80) As shown in FIG. 4-7, in at least some examples, the resulting butt weld joint **410** between two components **402**, **404** may be reinforced with seam tape. One way of reinforcing the weld while maintaining the low profile flush surface is to laminate or cover it with a tape **420** formed of a thermoplastic film or sheet. In some examples, tape **420** is formed of a seam reinforcing tape such as Sewfree® tapes provided by Bemis. The tape may serve to reinforce seams created by ultrasonic or laser equipment. The ultrasonically bonded seam may require additional strength and may not be not be entirely waterproof. Reinforcing tapes may be applied to the seams to create superior seam strength and further weatherproof the joint without adding significant bulk. In some examples, the tape may have a thickness of between about 0.1 mm and about 1 mm. The tape may also be formed of multi-layered thermoplastic adhesive film or from coated fabrics. In this manner, tapes may be applied to the joint to prevent water from soaking through the joint and may be applied by using a hot air taping machine. Tape **420** may also be formed of heat seal seam tape.

(81) Additionally, in some examples, tape is overlaid with a thin fabric layer **430** having a thickness of about 0.1 mm and about 1 mm to maintain a desirable soft surface finish. Such thermoplastic sheets **430** might be made from, for example: polyurethane (TPU), polyester, polyamide, polyolefin and aliphatic urethanes. These materials may be customised to provide the optimum performance characteristics for specific applications, and can be produced in a range of colours, opacities, and surface finishes required for the end use of patient interface equipment for the treatment of sleep disordered breathing, such as in headgear or a mask arrangement.

(82) As shown in FIG. 4-8, in some examples, in order to create a hinge, headgear components **402**, **404**, **406** may be placed in an ultrasonic welding tool without first welding them together. The components may be sandwiched together between two pieces of seam tape **420** or heat fusible fabric. The resulting joint may have a thinner bridge in between the headgear pieces that make up a larger component, creating an area of high flexibility **450** that may function as a hinge.

(83) 3.1.2 Multiple Vectors

(84) A multiple strap section **500** includes a first strap **502**, a second strap **504** and a third strap **506**, as shown in FIG. 5. The second strap **504** includes an attachment member **504-1** for connection to headgear or another securing device. The third strap **506** includes a similar attachment member **506-1**. V1 and V2 represent respective vectors for the second and third straps **504**, **506** and indicate a direction of the force applied to the straps by the headgear or securing device. Although the

vector for the first strap **502** is not shown, it will be appreciated from FIG. 5 that the first, second and third straps **502**, **504**, **506** each have different vectors.

(85) The straps **502**, **504**, and **506** are overlaid in an ultrasonic welding tool to form a first joint **510** and a second joint **512**. The first joint **510** interconnects the first strap **502** and the second strap **540**, while the second joint **512** interconnects the second strap **504** and the third strap **506**. Thus, the first, second and third straps **502**, **504**, **506** can be combined, without a significantly raised structure (as required with stitching), to provide multiple vectors in a multiple strap section **500** having a single thickness. If desired, the straps may have different thicknesses; as described above, the patient interfacing surfaces of the straps may still provide an even contact surface for the patient. The joints may be reinforced on either or both of the patient interface surface of the outer surface of the component by affixing seam tape over the join, that is, by pressing a composite of a thin fabric layer with a layer of heat-activated glue to the joint under a hot plate, heat fusing press, an iron, or a roller with hot air outlet.

(86) 3.1.3 Hinge or Flex Point

(87) The ultrasonic welding process may form a joint embodied as a thinned region, where the thickness of the component is smaller than the surrounding portions of the component, such as in a narrow channel on one or both surfaces of the component, which may function as a flex point or hinge (e.g., a living hinge) to provide flexibility where desired.

(88) Turning to FIG. 6, a headgear section **600** includes a first component **602**, a second component **604**, a third component **606**, a fourth component **608** and a fifth component **610**. A first joint **622** interconnects the first component **602** and the second component **604**. A second joint **624** interconnects the second component **604** and the third component **606**. A third joint **626** interconnects the third component **606** and the fourth component **608**, and a fourth joint **628** interconnects the fourth component **608** and the fifth component **610**.

(89) Joints may be arranged in relation to one another to allow a headgear section to adapt to a particular three-dimensional shape. As shown in FIG. 6, the first joint **622** and the second joint **624** are arranged to intersect and may form an angle there between. Thus, it may allow the first component **602**, the second component **604** and the third component **606** to flex in a particular angled manner. The third and fourth joints **626**, **628** have a different angled (e.g., non-parallel and non-intersecting) relation allowing the third component **606**, the fourth component **608** and the fifth component **610** to flex in a different manner. Intersecting joints and non-intersecting joints provide different methods of flexion. Because many of the joints described above are substantially flat, intersecting joints may be formed of multiple joints at the same location, affording greater variation for the final shape of the headgear. In this manner, it may be possible to overlap multiple components and insert a joint in between an existing joint simply because the joints are flush and thus sit flat. This may be useful when creating a textile mask of a complex shape requiring multiple overlapping joints.

(90) 3.1.4 Rolled Edge

(91) Rolled or rounded portions may be ultrasonically welded to flat headgear portions to provide rounded edges which may enhance comfort for the patient and substantially prevent facial marking.

(92) In FIG. 7-1, a headgear section **700** (e.g., a strap) includes a flat portion **702** and rolled portions **704** ultrasonically welded to ends of the flat portion **702**. In the illustrated example, the headgear section **700** is a strap. The flat portion may be a soft fabric layer and the rolled portions may be a fabric/foam composite. The flat portion **702** may be a low profile section in order to reduce bulk. The rolled portions **704** prevent edges of the flat portion **702** from contacting the patient's skin **720** which may otherwise cause irritation or facial marking, as shown in FIG. 7-2. Rolled portions **704** may be formed by ultrasonically welding the rolled portion along its edge, which is then ultrasonically welded to ends of the flat portion **702**. A joint **712** interconnects the flat portion **702** and the rolled portions **704**.

(93) The joint **712** is a low-profile joint such that there are no edges or sharp or raised seams which

may degrade comfort. Further, unlike stitching, there are no raised or loose threads above the surface which may irritate the patient.

(94) 3.1.5 Nested Fastening Member

(95) An ultrasonic welding process may be used to nest a fastening member, such as hook material (e.g., VELCRO® brand fasteners), within a strap such that the hook material is recessed in the strap. Referring to FIG. 8-1, a strap **800** and a hook material section **804** may be placed in the ultrasonic welding tool similar to that described in FIG. 1-3. The ultrasonic welding tool may remove a portion of the strap leaving behind a hole **802** in which the hook material is disposed. As shown in FIG. 8-2, the hook material **804** is nested within the hole **802** and is further ultrasonically welded to the strap. Resulting joints **806** interconnect the strap **800** and the hook material **804**.

(96) By nesting the hook material within the strap, the likelihood of the hook material **804** abrading the patient's skin or catching the patient's hair is considerably reduced since the hook material is in a plane that is offset from a plane of the remaining part of the strap that contacts the patient's face.

(97) 3.1.6 Controlled Flex Region

(98) Materials having differing degrees of flexibility may be ultrasonically welded to one another in an alternating manner to form a controlled flex region. Referring to FIG. 9, a component **900** includes a more rigid, less flexible member **902** and a more flexible, less rigid member **904** ultrasonically welded to one another in an alternating manner thereby forming a plurality of joints **906** which interconnect the members. The more rigid, less flexible member **902** may be foam, and the more flexible, less rigid member **904** may be a textile. The alternating textiles may allow flexibility in the component **900** in the manner of a gusset.

(99) As shown in FIG. 9, each foam member **902** and each textile **904** may be shaped to provide flexibility or rigidity as desired. In the illustrated example, the foam members **902** and the textile member **904** have varying shapes.

(100) 3.1.7 Comfort Pad

(101) A comfort pad may be constructed by an ultrasonic welding process. A patient may overwrap a headgear strap with a comfort pad in order to enhance comfort. A cushioned section of the comfort pad may be situated between the strap and the patient to lessen the pressure of the strap against the patient's skin.

(102) Turning to FIGS. 10-1 and 10-2, a comfort pad **1000** may include a padded section **1002** and a flat section **1012**. The padded section may include an outer fabric and an inner cushion layer (e.g., foam). The flat section **1012** is used to overwrap a strap and may include hook material **1016** on an inner surface to cooperate with unbroken loop **1014** on an opposing outer surface. The flat section **1012** may be a fabric and may further be constructed as a low profile section to reduce bulk.

(103) The padded section **1002** may be ultrasonically welded to the flat section **1012** to form a joint **1018** which interconnects the padded section and the flat section. The joint **1018** may be a seamless flush joint that provides a smooth surface which may comfortably contact the patient's skin without causing any or substantial irritation.

(104) In another example shown in FIGS. 11-1 to 11-3, a comfort pad **1100** may include a first flat section **1112** and a second flat section **1113** on opposite sides of a padded section **1102**. This arrangement may enable the comfort pad to more easily wrap around a strap **1130**. Similar to the comfort pad **1000**, the padded section **1102** may include an outer fabric and an inner cushion layer **1106** (e.g., foam). Further, the first flat section **1112** may include hook material **1116** on an inner surface to cooperate with unbroken loop **1114** on an outer surface of the section flat section **1113**. The first and second flat sections may be formed of fabric and may further be constructed as low profile sections to reduce bulk.

(105) A first joint **1118** interconnects the first flat section **1112** and the padded section **1102**, and a second joint **1120** interconnects the second flat section **1113** and the padded section. The joints **1118**, **1120** are flush joints that provide smooth surfaces which may comfortably contact the

patient's skin **1140** without causing any or substantial irritation.

(106) 3.1.8 Mask

(107) In an example, generally planar components may be formed into a three-dimensional mask by an ultrasonic welding process. It should be noted that the components may have a shape that is not planar. Referring to FIGS. **12-1** and **12-2**, a first component **1202** and a second component **1204** may be overlapped in an ultrasonic welding tool and joined along the curved weld line **1205**. The ultrasonic welding procedure yields a mask component **1210** which includes a joint **1212** that interconnects the first and second components **1202**, **1204**. The curved nature of the joint **1212** facilitates a three-dimensional shape when the first and second components **1202**, **1204** are pivoted with respect to one another along the joint **1212**, as can be seen in FIG. **12-3**.

(108) Dart lines **1222**, **1224** may be marked on the mask component **1210**. The mask component is then later folded along the dart lines to form darts **1232**, **1234**, which are in turn ultrasonically welded to create a three-dimensional shape in the mask component **1210**. The excess fabric in darts **1232** and **1234** may or may not be removed in the process. The ultrasonic weld forms joints **1242**, **1244**, as shown in FIGS. **12-3** and **12-4**.

(109) The three-dimensional shape in the mask component **1210** may form a cavity that supplies pressurized air to a patient. In the illustrated example, the mask component **1210** forms a nasal mask **1248** that seals against a patient's face. Alternatively, the mask **1248** may be a full face mask or other type of mask.

(110) Further, the nasal mask **1248** may be connected to conduits to form a nasal mask assembly **1250**. In the illustrated example, cuffs **1262** connect the mask assembly to conduit headgear **1270** (or other gas supply conduits). The conduit headgear **1270** function to at least partially support the mask assembly **1250** on the patient's face while also supplying pressurized air to the patient. It is noted that other conduits and/or headgear may also be used. The conduit headgear **1270** may be ultrasonically welded to the cuffs **1262**, thus forming ultrasonic welding joints **1272**, and the cuffs **1262** may be ultrasonically welded to the nasal mask **1248** to form joints **1274**.

(111) 4. Ultrasonic Welding to Create Multiple Component Depth

(112) Components may also be stacked and ultrasonically welded one on top of the other. For example, components may be joined only at their ends such that a space is formed between the components. Alternatively, components may be joined in a manner that does not provide a space.

(113) 4.1 Pocket

(114) A component **1302** may be ultrasonically welded to a second component, e.g., a pocket fabric **1308** to form a pocket component **1310** having a space or pocket **1312** therebetween, as shown in FIG. **13-1**. The component **1302** may include inner **1303** and outer **1304** fabric layers and an inner cushion layer **1305**. The cushion layer **1305** may be foam or spacer fabric. The inner and outer layers **1303**, **1304** may be formed of a nylon/spandex or elastane combination. In an alternative form, there may be one or two additional layer/s of a heat-fixable TPU (or other thermosensitive polymer) glue sheet welded in between component **1302** and pocket fabric **1308** during the process. This may permit later inserting of a rigidizer component (**1342** FIG. **13-2**) and affixing a curved or flat rigidizer in place by applying heat and thus melting the TPU glue sheet inside the pockets so as to fuse all of the components together.

(115) The component **1302** may be ultrasonically die cut and welded to round its edges, and the pocket fabric **1308** may be ultrasonically welded to the component **1302** to form joints **1314**. The joints **1314** form smooth, flush joints that may enclose the cushioning layer. Since the component **1302** and the pocket fabric **1308** are welded only at their ends, a pocket **1312** is formed between the component and the pocket fabric.

(116) As shown in FIG. **13-2**, a pocket **1339** formed between a headgear component **1332** and a pocket fabric **1338** may be used to accommodate a rigidizer **1340**. The rigidizer may be formed by injection molding and may further include a clip **1342** for connecting the headgear component to another device such as a mask, held in place by the headgear component. The connection between

the headgear component **1332** and the other device may be strengthened by the clip **1342** which is formed of a more rigid material than the headgear component.

(117) In another example, shown in FIG. **13-3**, the headgear component **1332** includes inner and outer layers **1333**, **1334** and a cushion layer **1335**. The headgear component **1332** may be thermoformed with the rigidizer **1340** positioned in the pocket **1339** to fix the rigidizer to the headgear component. The thermoforming process melts a portion of the rigidizer which hardens to secure the rigidizer to the headgear component. Alternatively, the pocket may include an adhesive to secure the rigidizer.

(118) In the example shown in FIG. **13-4**, the ultrasonic welding joints **1314** may be located on the outer surface of the component **1302-B** away from a patient contacting surface of the component **1302-B**. The joints **1314** form smooth, flush joints. Positioning the seams on the outer surface of the component **1302** may enhance comfort by providing a larger continuous surface of the cushioning fabric as a patient contacting surface. It will also provide more cushioning, and may help to relieve facial marking. This example may help create a more rounded edge external profile as shown in FIG. **13-4**. A curved profile strap with a rounded edge profile near the patient side is shown in the relaxed condition in FIG. **13-5** and FIG. **13-6** in the compressed condition. For example, the ratio of the width of portion **1302-A** to that of the width of **1302-B** is less than unity. In FIG. **13-6** the ratio is closer to unity than in FIG. **13-5**.

(119) 4.1.1 Strap Tidy

(120) In another example, a strap of a headgear may be attached to a strap tidy capable of containing the strap as shown in FIG. **14**. A pocket **1408** may be formed between a strap **1402** and a piece of fabric or strap tidy **1404** to create a space to hold a loose or free end of the strap **1402**. The strap tidy **1404** may be ultrasonically welded to the strap **1402** to form joints **1406**, the joints **1406** forming at least one pocket **1408** for accepting the loose or free end of a strap.

(121) 4.2 Soft Patient Interface

(122) Alternatively, components may be stacked one on top of the other and ultrasonically welded together in a manner that leaves no space therebetween. In an example shown in FIG. **15-1**, a headgear component **1502** has inner, outer and cushion layers similar to headgear component **1332**. A patient interface component **1504** may be ultrasonically welded to the headgear component **1502** to provide a more comfortable patient interfacing surface. The patient interface component **1504** may be constructed of a soft material, e.g., a soft fabric. The patient interface component **1504** may be welded to the headgear component **1502** at several points or continuously along an inner surface of the patient interface component **1504** and an outer surface of the inner layer of the headgear component **1502**. For example, the patient interface component may be a side portion of a mask.

(123) 5. Manufacturing

(124) Preferably, the method of manufacturing components may reduce costs by maximizing volume and eliminating material waste. For example, headgear may be designed to have a plurality of common parts such that a plurality of components may have an identical geometry and be located in different sections of the headgear. For instance, headgear **1600** in FIG. **16-1** includes a headgear first component **1602**, headgear second component **1604**, and headgear third component **1606**. Although the portion of headgear **1600** shown in FIG. **16-1** includes seven parts, only three different geometries need to be manufactured to fulfill the parts requirement. Thus, fewer individual component designs are required which may reduce cost.

(125) Further, components may be shaped such that they can be nested on the bulk material, such that when they are die cut into individual components, waste is reduced thereby further reducing cost. As an example, headgear fourth component **1622** and headgear fifth component **1624** may be nested to increase yield, as shown in FIG. **16-2**. The component parts in FIG. **16-1** may be ultrasonically welded to form joints **1610**.

(126) In the foregoing description and in the accompanying drawings, specific terminology, equations and drawing symbols are set forth to provide a thorough understanding of the present

technology. In some instances, the terminology and symbols may imply specific details that are not required to practice the technology. For example, although the terms “first” and “second” may be used herein, unless otherwise specified, the language is not intended to provide any specified order but merely to assist in explaining distinct elements of the technology. Moreover, while the technology has been described in connection with several examples, it is to be understood that the technology is not to be limited to the disclosed examples, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the technology. Also, the various examples described above may be implemented in conjunction with other examples, e.g., one or more aspects of one example may be combined with one or more aspects of another example to realize yet other examples. Further, each independent feature or component of any given assembly may constitute an additional example. In addition, while the technology has particular application to patients who suffer from OSA, it is to be appreciated that patients who suffer from other illnesses (e.g., congestive heart failure, diabetes, morbid obesity, stroke, bariatric surgery, etc.) can derive benefit from the above teachings. Moreover, the above teachings have applicability with patients and non-patients alike in non-medical applications.

Claims

1. A method of making a comfort pad for use with headgear in holding a respiratory mask in position on a patient's face, comprising: ultrasonically welding a padded member to a first substantially flat member thereby forming a first ultrasonic welding joint at a first end of the first substantially flat member, whereby the first ultrasonic welding joint interconnects the padded member and the first substantially flat member, wherein the padded member is arranged to provide a cushion between the patient and the headgear, and the first flat member is arranged to overwrap a headgear component of the headgear to position the padded member, and wherein the first flat member includes hook material and/or unbroken loop at a second end of the first flat member opposite from the first end.
2. The method of making a comfort pad according to claim 1, wherein the padded member includes a foam layer.
3. The method of making a comfort pad according to claim 1, further comprising ultrasonically welding a second substantially flat member to the padded member thereby forming a second ultrasonic welding joint, the second flat member being joined to the padded member on an opposite side of the padded member than the first flat member.
4. The method of making a comfort pad according to claim 1, wherein the headgear component is a strap of the headgear.
5. The method of making a comfort pad according to claim 1, wherein the first ultrasonic welding joint is a flush joint that provides a smooth surface for contacting the patient's skin.
6. A comfort pad for use with headgear in holding a respiratory mask in position on a patient's face, comprising: a padded member and a first substantially flat member, wherein the padded member is ultrasonically welded to the first flat member thereby forming a first ultrasonic welding joint at a first end of the first substantially flat member, whereby the first ultrasonic welding joint configured to interconnect the padded member and the first substantially flat member, wherein the padded member is arranged to provide a cushion between the patient and the headgear, and the first flat member is arranged to overwrap a headgear component of the headgear to position the padded member, and wherein the first flat member includes hook material and/or unbroken loop at second end of the first flat member opposite from the first end.
7. The comfort pad according to claim 6, wherein the padded member includes a foam layer.
8. The comfort pad according to claim 6, further comprising a second substantially flat member, wherein the second flat member is ultrasonically welded to the padded member thereby forming a second ultrasonic welding joint, the second flat member being joined to the padded member on an

opposite side of the padded member than the first flat member.

9. The comfort pad according to claim 6, wherein the headgear component is a strap of the headgear.

10. The comfort pad according to claim 6, wherein the padded member has a single substantially flat member comprising the first substantially flat member.
