

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12404867
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Renaud; Philippe et al.

Wheels having a bi-layered coating including a hard coating layer and methods for making the same

Abstract

A wheel includes a hub portion configured to rotate about a rotational axis. A plurality of blades extends radially outward from the hub portion. Each blade of the plurality of blades includes a leading edge and a trailing edge. The hub portion and the plurality of blades include a substrate metal that includes aluminum or an alloy thereof. The substrate metal of the plurality of blades has coated directly thereon a first coating layer including electroless nickel-phosphorous. The first coating layer has coated directly thereon a second hard coating layer that overlies the leading edges of the plurality of blades and that is formed of a physical vapor deposition-compatible material.

Inventors: Renaud; Philippe (Sanchey, FR), Murukesan; Palaniappa (Bangalore, IN)

Applicant: Garrett Transportation I Inc. (Torrance, CA)

Family ID: 92634791

Assignee: Garrett Transportation I Inc. (Torrance, CA)

Appl. No.: 18/333129

Filed: June 12, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240301887 A1	Sep. 12, 2024

Foreign Application Priority Data

IN	202311016220	Mar. 10, 2023
----	--------------	---------------

Publication Classification

Int. Cl.: F04D29/02 (20060101)

U.S. Cl.:

CPC **F04D29/023** (20130101); F05D2230/31 (20130101); F05D2230/90 (20130101); F05D2300/611 (20130101)

Field of Classification Search

CPC: F04D (29/023); F05D (2230/31); F05D (2230/90); F05D (2300/611); F05D (2220/40); F01D (5/288)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5441024	12/1994	Wetig et al.	N/A	N/A
6754954	12/2003	Decker et al.	N/A	N/A
11566631	12/2022	Murukesan et al.	N/A	N/A
2008/0278029	12/2007	Pardo	205/112	C23C 18/1605
2010/0098532	12/2009	Diemer et al.	N/A	N/A
2010/0148129	12/2009	Kosowsky et al.	N/A	N/A
2010/0159271	12/2009	Sugioka	428/650	F04B 27/0886
2011/0002067	12/2010	Allen	N/A	N/A
2011/0229338	12/2010	Voong et al.	N/A	N/A
2014/0178637	12/2013	Rajagopalan et al.	N/A	N/A
2014/0186174	12/2013	Malfa	N/A	N/A
2014/0272166	12/2013	Shim	427/256	F01D 5/288
2014/0339699	12/2013	Arvin et al.	N/A	N/A
2015/0004021	12/2014	Kang	417/410.1	F04B 39/122
2015/0111061	12/2014	Shen	148/121	C22C 19/07
2015/0118090	12/2014	Lachey et al.	N/A	N/A
2015/0132539	12/2014	Bailey et al.	N/A	N/A
2017/0009350	12/2016	Myllymaki et al.	N/A	N/A
2017/0283220	12/2016	Ding et al.	N/A	N/A
2018/0045215	12/2017	Arai et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
201900007758	12/2019	IT	N/A

OTHER PUBLICATIONS

Hadipour et al., "Comparison of H—Cr single layer and Ni-PIH-Cr duplex coating," Surface Engineering, vol. 31, Feb. 29, 2016, p. 665-672. cited by applicant

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

(1) This application is related to and claims all available benefit of Indian Provisional Patent Application IPA: 202311016220 filed Mar. 10, 2023, the entire contents of which are herein incorporated by reference.

TECHNICAL FIELD

(2) The present disclosure generally relates to wheels for turbo-devices, for example, turbochargers, turbines or turbomachines, and/or the like. More particularly, the present disclosure relates to wheels having a bi-layered coating of an electroless nickel-phosphorous base layer and a hard coating top layer formed thereon and methods for making the same.

BACKGROUND

(3) Turbo-devices can be used in a variety of applications. For example, turbochargers for gasoline and diesel internal combustion engines are devices known in the art that are used for pressurizing or boosting the intake air stream, routed to a combustion chamber of the engine, by using the heat and volumetric flow of exhaust gas exiting the engine. Another example includes turbines or turbomachines for fuel cells. The turbine may be operatively connected to a fuel cell system and may be configured as an e-charger, electric turbocharger, or other turbo-device for the fuel cell.

(4) In the case of turbochargers for internal combustion engines, the exhaust gas exiting the engine is routed into a turbine housing of a turbocharger in a manner that causes an exhaust gas-driven turbine wheel to spin within the housing. The exhaust gas-driven turbine wheel is mounted onto one end of a shaft that is common to a radial air compressor mounted onto an opposite end of the shaft and housed in a compressor housing. Thus, rotary action of the turbine wheel also causes the air compressor to spin within a compressor housing of the turbocharger that is separate from the turbine housing. The spinning action of the air compressor causes intake air to enter the compressor housing and be pressurized or boosted to a desired amount before it is mixed with fuel and combusted within the engine combustion chamber.

(5) In recent years, there has been increasing pressure in the form of governmental legislation to reduce internal combustion engine emissions, such as NO_x and particulate matter (PM). Oxides of nitrogen (NO_x) may be formed when temperatures in the combustion chamber are about 2500° F. or hotter. At these elevated temperatures, the nitrogen and oxygen in the combustion chamber may chemically combine to form nitrous oxides.

(6) Exhaust gas recirculation (EGR) is a method that has been used to reduce the level of NO_x in exhaust gases. In EGR systems, some of the exhaust gases that would otherwise be discharged into the environment are recirculated into the intake stream. The recirculated exhaust gases have already combusted and have a significantly lower oxygen content, so they do not burn again when they are recirculated. The exhaust gases may displace some of the normal intake charge. As a result, the combustion process may be cooler by several hundred degrees so that NO_x formation may be reduced.

(7) The use of EGR, however, results in an increased amount of water that is condensed out of the recirculated exhaust gasses. The amount of water that is condensed may depend, for example, on temperature, humidity, and operating speed of the engine. When present, the condensed water droplets in the intake stream are passed through an inlet and impact the spinning compressor wheel, and as a result, an erosive effect may be observed over time. This can cause the components to

prematurely fail.

(8) Similarly in turbines for fuel cells, when present, condensed water droplets in the intake stream are passed through an inlet and impact the spinning fuel cell turbine wheel, and as a result, an erosive effect may also be observed over time. As a result, such components as well may prematurely fail.

(9) Accordingly, it is desirable to provide wheels for turbo-devices that are able to withstand the erosive effects of water droplets, without requiring the use of heavier and relatively expensive materials. Furthermore, other desirable features and characteristics of the inventive subject matter will become apparent from the subsequent detailed description of the inventive subject matter and the appended claims, taken in conjunction with the accompanying drawings and this background of the inventive subject matter.

BRIEF SUMMARY

(10) Wheels having a bi-layered coating of an electroless nickel-phosphorous base layer and a hard coating top layer formed thereon and methods for making the same, are disclosed herein.

(11) In an exemplary embodiment, a wheel includes a hub portion configured to rotate about a rotational axis. A plurality of blades extends radially outward from the hub portion. Each blade of the plurality of blades includes a leading edge and a trailing edge. The hub portion and the plurality of blades include a substrate metal that includes aluminum or an alloy thereof. The substrate metal of the plurality of blades has coated directly thereon a first coating layer including electroless nickel-phosphorous. The first coating layer has coated directly thereon a second hard coating layer overlaying the leading edges of the plurality of blades and formed of a physical vapor deposition (PVD)-compatible material.

(12) In another exemplary embodiment, a wheel includes a hub portion configured to rotate about a rotational axis. A plurality of blades extends radially outward from the hub portion. Each blade of the plurality of blades includes a leading edge and a trailing edge. The hub portion and the plurality of blades include a substrate metal that includes aluminum or an alloy thereof. The substrate metal of the plurality of blades has coated directly thereon a first coating layer including electroless nickel-phosphorous. The first coating layer has coated directly thereon a second hard coating layer overlaying the leading edges of the plurality of blades. The second hard coating layer has a hardness of greater than about 800 HV and includes a material chosen from the group of carbides, nitrides, diamond like carbon (DLC), or combinations thereof. The leading edges are positioned longitudinally forward from the trailing edges of the plurality of blades along the rotational axis with respect to a flow of air along the wheel when the wheel is rotating. The second hard coating layer has a thickness along the leading edges of from about 1 to about 10 microns and the thickness reduces in a gradually tapering manner rearward towards the trailing edges such that the thickness of the second hard coating layer is zero microns at or longitudinally forward of the trailing edges of the plurality of blades.

(13) In another exemplary embodiment, a method for making a wheel includes providing a substrate wheel. The substrate wheel includes a hub portion configured to rotate about a rotational axis. A plurality of blades extends radially outward from the hub portion. Each blade of the plurality of blades comprises a leading edge and a trailing edge. The hub portion and the plurality of blades include a substrate metal that includes aluminum or an alloy thereof. The method further includes forming on the substrate metal of the hub portion and the plurality of blades a first coating layer including electroless nickel-phosphorous. Forming the first coating layer includes immersing the substrate wheel in an electroless nickel-phosphorous plating bath that includes nickel cations and phosphorous oxide anions and subsequently, exposing the substrate wheel including the first coating layer to a heat treatment process to thereby increase adhesion strength of the first coating layer to the substrate metal. The method further includes forming a second hard coating layer from a physical vapor deposition (PVD)-compatible material on the first coating layer overlying the leading edges of the plurality of blades.

(14) This summary is provided to introduce a selection of concepts in a simplified form that are further described below in the detailed description. This summary is not intended to identify key features or essential features of the claimed subject matter, nor is it intended to be used as an aid in determining the scope of the claimed subject matter.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The inventive subject matter will hereinafter be described in conjunction with the following drawing figures, wherein like numerals denote like elements, and wherein:

(2) FIG. 1 is a perspective view of a wheel operatively disposed in a turbo-device, which is schematically illustrated, in accordance with some embodiments of the present disclosure;

(3) FIG. 2 is a perspective view of a wheel operatively disposed in a turbo-device, which is schematically illustrated, in accordance with some embodiments of the present disclosure; and

(4) FIG. 3 is a flowchart illustrating a method for making a wheel in accordance with some embodiments of the present disclosure.

DETAILED DESCRIPTION

(5) The following detailed description is merely exemplary in nature and is not intended to limit the invention or the application and uses of the invention. As used herein, the word “exemplary” means “serving as an example, instance, or illustration.” Thus, any embodiment described herein as “exemplary” is not necessarily to be construed as preferred or advantageous over other embodiments. All of the embodiments described herein are exemplary embodiments provided to enable persons skilled in the art to make or use the invention and not to limit the scope of the invention which is defined by the claims. Furthermore, there is no intention to be bound by any expressed or implied theory presented in the preceding technical field, background, brief summary, or the following detailed description.

(6) Unless specifically stated or obvious from context, as used herein, the term “about” is understood as within a range of normal tolerance in the art, for example within 2 standard deviations of the mean. “About” can be understood as within 10%, 5%, 1%, 0.5%, 0.1%, 0.05%, or 0.01% of the stated value. “About” can alternatively be understood as implying the exact value stated. Unless otherwise clear from the context, all numerical values provided herein are modified by the term “about.”

(7) The present disclosure is generally directed to wheels for turbo-devices in which the wheels have a bi-layered coating of an electroless nickel-phosphorous base layer and a hard coating top layer, and methods for making the same. In particular, the present disclosure addresses the aforementioned erosion problem with the use of electroless nickel-phosphorus as a base layer followed by a hard coating top layer. The purpose of the electroless nickel-phosphorous layer as a base layer is to minimize the difference in hardness between the relatively hard coating top layer and the relatively soft aluminum substrate. That is, a hard coating top layer disposed directly on the soft aluminum substrate could potentially compromise fatigue properties due to a poor combination of mechanical strength and coefficient of thermal expansion mismatch between the aluminum substrate and the hard coating top layer.

(8) The present disclosure utilizes a relatively high phosphorus content (for example, greater than or equal to about 10 wt. %) electroless nickel-phosphorous coating as the base coating. The combination of a relatively high phosphorus content and controlled process parameters ensures a compressive residual stress in the coating that will help to reduce potential issues of the wheel due to fatigue. The aforesaid base layer of electroless nickel-phosphorous covers the entire wheel (e.g., hub portion and blades), with the exception of several functional regions for reasons of manufacture/assembly. The functional regions not requiring the coating are masked during the

process. As will be discussed in further detail below, in some embodiments, the wheel is subjected to a heat treating process after deposition of the electroless nickel-phosphorous to improve adhesion.

(9) To provide additional hardness, the aforesaid hard coating layer is employed, which has a hardness greater than about 800 HV, or greater than about 900 HV. In accordance with some embodiments, the hard coating layer is provided only on the leading edge regions of the blades of the wheel, using a physical vapor deposition (PVD) technique(s). This selective provision is achieved by positioning the wheel in an PVD vacuum cell in a manner such that the leading edges face the deposition electrode surface, focusing a deposition of PVD-compatible material(s) towards and onto the leading edges. The PVD deposition process is performed such that the thickness of the hard coating layer is greatest at the leading edges (for example, a thickness from about 1 to about 10 microns) and then gradually decreases (in a tapering manner) towards the back-disc of the wheel. Erosion from water droplets has been found to be greatest at the leading edges. At the fillet root (e.g., transition region between the blades and hub portion), which is the area of maximum stress during operation, the thickness is reduced to about 0 microns, such that the effect of tensile stresses caused by the additional of the hard coating layer is effectively eliminated at those locations.

(10) Referring to FIG. 1, a perspective view of a wheel **10** operatively disposed in a turbo-device **12** is provided. In the illustrated embodiment, the turbo-device **12** is configured as a turbocharger **14** for an internal combustion engine and the wheel **10** is configured as a turbocharger compressor wheel **16**. A non-limiting example of turbochargers for internal combustion engines including turbocharger compressor wheels is described in U.S. Pat. No. 11,566,631, filed on Mar. 29, 2021, which is owned by the assignee of the present application and is hereby incorporated by reference in its entirety for all purposes.

(11) As illustrated, the wheel **10** is operatively disposed in the turbo-device **12** between an inlet **18** and an outlet **20** to rotate (indicated by single headed arrow **13**) about a rotational axis **22**. The wheel **10** is a radial wheel that includes a hub portion **24** and a plurality of blades **26** that extend radially outward from the hub portion **24**. The blades **26** have a backward curvature rather than being configured to extend in a purely radial blade configuration. Each blade **26** includes a leading edge **28** that is in fluid communication with the inlet **18** and a trailing edge **30** that is in fluid communication with the outlet **20**. The leading edges **28** define the beginning of an intake area for the combined set of blades **26**, extending through the circular paths of roughly the upstream $\frac{1}{3}$ of the blades **26**. The trailing edges **30** define the end of an annular output area for the combined set of blades **26**, extending through the circular paths of roughly the downstream $\frac{1}{3}$ of the blades **26**.

(12) During operation of the turbo-device **12**, the wheel **10** rotates about the rotational axis **22** and the leading edges **28** receive intake air that passes through the inlet **18** and advances rearwardly (indicated by single headed arrow **32**) along the blades **26** towards the trailing edges **30**. As such, the leading edges **28** are positioned longitudinally forward of the trailing edges **30** of the blades **26** with respect to the rotational axis **22** and the flow of air **32** along the wheel **10**. As noted above, the wheel **10** is a turbocharger compressor wheel **16** in which the blades **26** are configured to compress the intake air to form compressed or pressurized air. The pressurized air passes from the trailing edges **30** and is ejected out through the outlet **20**.

(13) In some embodiments, the hub portion **24** and the blades **26** are formed of a substrate metal **36**, such as, aluminum or an aluminum alloy, for example, via a casting and/or machining process. The wheel **10** is provided with a first (base) coating layer **34** on and overlying the substrate metal **36** and includes electroless nickel-phosphorous. The phosphorous content of the first coating layer **34** may be greater than or equal to about 10 wt. %, for example from about 10 to about 15 wt. %, such as from about 11 to about 15 wt. %, or about 12 to about 15 wt. %. The thickness of the first coating layer **34** may be from about 5 to about 30 microns, for example about 10 to about 30 microns. The first coating layer **34** may be provided on all or most of the surfaces of the wheel **10**,

both forward and rear facing. If the first coating layer **34** is not provided on all of the surfaces, the surfaces not coated with the first coating layer **34** may include functional surfaces, such as portions of the back facing hub portion **24** about the centerline (axis of rotation **22**) or portions of the forward facing hub portion **24**. As will be discussed in further detail below, in some embodiments, the wheel **10** has been subjected to a heat treating process after deposition of the electroless nickel-phosphorous to improve adhesion of the first coating layer **34** to the substrate metal **36**.

(14) The wheel **10** is provided with a second (top) hard coating layer **38** on and overlying portions of the first coating layer **34** and includes or is formed of a hard, physical vapor deposition (PVD)-compatible material. As used herein, the phrase “PVD-compatible material” is understood to mean a material(s) or compound(s) that can be formed by but not necessarily limited to a PVD process using one or more precursor materials.

(15) The second hard coating layer **38** has a thickness over the first coating layer **34** that varies gradually (in a tapering manner) across the forward-facing surfaces of the wheel **10** including the blades **26**. In an embodiment, the thickness of the second hard coating layer **38** is greatest at the leading edges **28**. This greatest thickness may be from about 1 to about 10 microns, such as about 1 to about 5 microns. The thickness of the second hard coating layer **38** gradually decreases from the leading edges **28** rearwardly in the direction towards of the trailing edges **30**, for example, along both sides (e.g., compression side and suction side) of each of the blades **26**. In embodiments, the thickness of the second hard coating layer **38** at the trailing edges **30** is 0 or about 0 microns. In such embodiments, it is not necessary that the thickness reach 0 microns exactly at the trailing edges **30** as it decreases from the leading edges **28**. Rather, the thickness of the second hard coating layer **38** may reach 0 microns at any percentage of the overall distance rearwardly from the leading edges **28** to the trailing edges **30** (e.g., longitudinally forward of the trailing edges **30**), for example from about 20% to about 80%, or about 30% to about 70%.

(16) In an embodiment, the PVD-compatible material that forms the second hard coating layer **38** is chosen from carbides, for example, chromium carbide (Cr.sub.3C.sub.2), silicon carbide (SiC), tungsten carbide (WC), zirconium oxycarbide (ZrOC), nitrides, for example, boron nitride (BN), chromium nitride (CrN), titanium nitride (TiN), titanium carbonitride (TiCN), zirconium nitride (ZrN), diamond like carbon (DLC), or combinations thereof. In an embodiment, the second hard coating layer **38** has a hardness of greater than about 800 HV, such as greater than about 900 HV, for example from about 1,000 to about 3,500 HV.

(17) Referring to FIG. 2, a wheel **100** that is operatively disposed in a turbo-device **112** between an inlet **118** and an outlet **120** is provided. In the illustrated embodiment, the turbo-device is a turbine **114** for fuel cells and the wheel **100** is configured as a fuel cell turbine wheel **116**. A non-limiting example of turbines for fuel cells including fuel cell turbine wheels is described in U.S. Patent Application Publication No. 2022/0006369, filed on Jul. 1, 2020, which is owned by the assignee of the present application and is hereby incorporated by reference in its entirety for all purposes.

(18) In particular, the wheel **100** including the rotational axis **122**, the hub portion **124**, the blades **126**, the leading edges **128**, the trailing edges **130**, the substrate metal **136**, the first coating layer **134**, and the second hard coating layer **138** are similarly configured to the wheel **10** as discussed above in relation to FIG. 1 including the rotational axis **22**, the hub portion **24**, the blades **26**, the leading edges **28**, the trailing edges **30**, the substrate metal **36**, the first coating layer **34**, and the second hard coating layer **38**, respectively, but with the exception that the blades **126** are configured to expand the intake air received from the inlet **118**, along the airflow direction **132** towards the trailing edges **130** to form an expanded or depressurized air. The expanded or depressurized air passes from the trailing edges **130** and is ejected out through the outlet **120**.

(19) Referring to FIG. 3, the compressor wheel **10**, **100** as discussed above may be made in accordance with a method **200** as illustrated in the flowchart. The method **200** includes a step **202** of providing a substrate wheel formed of a substrate metal, specifically a wheel made of aluminum (or alloy thereof) in the configuration discussed above in relation to FIGS. 1-2, with the exception

of the coating layers. The substrate wheel may be manufactured using conventional manufacturing processes, such as casting and/or machining, or the like.

(20) The method **200** continues with a step **204** of forming (e.g., via depositing) a first (base) electroless nickel-phosphorous coating layer onto the substrate metal of the substrate wheel. Electroless nickel-phosphorus plating is a chemical process that deposits an even layer of nickel-phosphorus alloy on the surface of the substrate metal. The process involves dipping the substrate wheel in a water solution containing a nickel salt and a phosphorus-containing reducing agent, for example a hypophosphite salt. The concentration of the phosphorous-containing reducing agent is selected so as to achieve a phosphorous amount in the first coating layer greater than or equal to about 10 wt. %, as described above. The reduction of the metal cations in solution to metallic form is achieved by purely chemical means, through an autocatalytic reaction. Before plating, the surface of the substrate may be cleaned. Cleaning may be achieved by a series of chemical baths, including non-polar solvents to remove oils and greases, as well as acids and alkalis to remove oxides, insoluble organics, and other surface contaminants. Further, functional portions of the substrate metal, as described above, may be optionally masked. Ingredients of the electroless nickel plating bath include a source of nickel cations Ni^{2+} , for example nickel sulfate and a suitable reducing agent, such as hypophosphite H_2PO_3^- . The plating bath may further include complexing agents, such as carboxylic acids or amines; stabilizers, such as lead salts or sulfur compounds; buffers; surfactants; and accelerators. The plating process is controlled with temperature and time to achieve a desired uniform thickness of about 20 to about 30 microns, as described above. Once Ni—P plating is complete, the substrate metal, now having the first coating layer plated thereon, may be rinsed to remove any residues from the plating process, and the masking (if any) may be removed. In an exemplary embodiment, after plating, the substrate wheel including the first electroless nickel-phosphorous coating layer is heat treated, for example at a temperature of from about 100 to about 150° C. for a time of from about 1 to about 4 hours, to increase the adhesion strength of the first electroless nickel-phosphorous coating layer to the underlying substrate metal.

(21) The method **200** continues with a step **206** of forming a second hard coating layer over the first Ni—P layer via a physical vapor deposition (PVD) process. As discussed above, the second hard coating layer is formed by depositing a PVD-compatible material that provides a hard coating layer, for example, greater than about 800 HV, or greater than about 900 HV, over the Ni—P layer. In particular, the PVD process is a vaporization coating technique, involving the transfer of material on an atomic level under vacuum conditions. The PVD precursor materials start out in a solid form and are vaporized and deposited onto the Ni—P coated substrate. The PVD process may include an initial step of placing the Ni—P coated substrate in a PVD vacuum chamber. The precursor material(s) that form the PVD-compatible material(s) is/are evaporated by a high energy source such as an electron beam. The vaporized material(s) is transported to the Ni—P coated substrate. A reaction occurs between the metal atoms and the appropriate reactive gas (such as oxygen, nitrogen, or methane) and the second hard coating layer is deposited onto the Ni—P coated substrate.

(22) In an embodiment, the PVD process includes processing conditions including a process deposition temperature of about 250° C. or less, for example, from about 70 to about 250° C. Advantageously, in some embodiments, depositing the PVD-compatible material on the first coating layer at the process deposition temperature of about 250° C. or less, helps ensure that the aluminum or aluminum alloy substrate metal is dimensionally, structurally, and/or mechanically unaffected or otherwise remains stable/unchanged.

(23) The method **200** may optionally include performing various finishing processes, such as final cleaning, polishing, machining, heat treatment at temperatures of up to about 250° C. (for example from about 200° C. to about 250° C.) for time period of about 1 hour to about 4 hours, such as about 2 hours to about 4 hours, and others as conventionally known in the art. The result is a wheel

10, 100 in accordance with that described above in connection with FIGS. 1-2.

(24) Accordingly, the present disclosure has provided wheels for turbo-devices having a bi-layered coating of an electroless nickel-phosphorous base layer and a hard coating top layer, and methods for making the same. The present disclosure has addressed the aforementioned erosion problem with the use of electroless nickel-phosphorus as a base layer followed by a hard coating top layer, located in greatest thickness near the leading edges of the blades. As such, the wheels of the present disclosure are able to withstand the erosive effects of water droplets, without requiring the use of heavier and more expensive materials, such as, for example, titanium. Moreover, the wheels disclosed herein are able to be manufactured easily with existing technologies, such as chemical deposition and physical vapor deposition that do not result in significant additional manufacturing complexity or expense.

(25) While at least one exemplary embodiment has been presented in the foregoing detailed description of the inventive subject matter, it should be appreciated that a vast number of variations exist. It should also be appreciated that the exemplary embodiment or exemplary embodiments are only examples, and are not intended to limit the scope, applicability, or configuration of the inventive subject matter in any way. Rather, the foregoing detailed description will provide those skilled in the art with a convenient road map for implementing an exemplary embodiment of the inventive subject matter. It being understood that various changes may be made in the function and arrangement of elements described in an exemplary embodiment without departing from the scope of the inventive subject matter as set forth in the appended claims.

Claims

1. A wheel comprising: a hub portion configured to rotate about a rotational axis; and a plurality of blades extending radially outward from the hub portion, wherein each blade of the plurality of blades comprises a leading edge and a trailing edge, wherein the hub portion and the plurality of blades comprise a substrate metal that comprises aluminum or an alloy thereof, wherein the substrate metal of the plurality of blades has coated directly thereon a first coating layer comprising electroless nickel-phosphorous that comprises a phosphorous content of 12 wt. % to 15 wt. %, and wherein the first coating layer is formed by electroless plating and is subsequently heat treated to enhance adhesion to the substrate metal, and wherein the first coating layer has coated directly thereon a second hard coating layer overlaying the leading edges of the plurality of blades and formed of a physical vapor deposition (PVD)-compatible material, wherein the second hard coating layer has a thickness that is greatest at the leading edges and decreases rearward in a gradually tapering manner such that the thickness is zero microns at or longitudinally forward of the trailing edges of the plurality of blades.
2. The wheel of claim 1, wherein the PVD-compatible material is chosen from the group of carbides, nitrides, diamond like carbon (DLC), or combinations thereof.
3. The wheel of claim 2, wherein the PVD-compatible material is chosen from the group of chromium carbide (CnC2), silicon carbide (SiC), tungsten carbide (WC), zirconium oxycarbide (ZrOC), boron nitride (BN), chromium nitride (CrN), titanium nitride (TiN), titanium carbonitride (TiCN), zirconium nitride (ZrN), DLC, or combinations thereof.
4. The wheel of claim 1, wherein the leading edges are positioned longitudinally forward from the trailing edges of the plurality of blades along the rotational axis with respect to a flow of air along the wheel when the wheel is rotating, and wherein the second hard coating layer has a thickness that is greatest at the leading edges and that decreases rearward towards the trailing edges.
5. The wheel of claim 4, wherein the thickness of the second hard coating layer along the leading edges of the plurality of blades is from about 1 microns to about 10 microns.
6. The wheel of claim 4, wherein the thickness of the second hard coating layer reduces in a gradually tapering manner rearward towards the trailing edges of the plurality of blades such that

the thickness of the second hard coating layer is zero microns at or longitudinally forward of the trailing edges of the plurality of blades.

7. The wheel of claim 1, wherein the first coating layer extends directly on the substrate metal of the hub portion.

8. The wheel of claim 7, wherein the first coating layer comprises electroless nickel-phosphorous having a constant thickness across the hub portion and the plurality of blades of from about 5 microns to about 30 microns.

9. The wheel of claim 1, wherein the second hard coating layer has a hardness of greater than about 800 HV.

10. The wheel of claim 1, wherein the second hard coating layer has a hardness of from about 1,000 HV to about 3,500 HV.

11. The wheel of claim 1, wherein the wheel is configured as a turbocharger compressor wheel or a fuel cell turbine wheel.

12. A wheel comprising: a hub portion configured to rotate about a rotational axis; and a plurality of blades extending radially outward from the hub portion, wherein each blade of the plurality of blades comprises a leading edge and a trailing edge, wherein the hub portion and the plurality of blades comprise a substrate metal that comprises aluminum or an alloy thereof, wherein the substrate metal of the plurality of blades has coated directly thereon a first coating layer comprising electroless nickel-phosphorous that comprises a phosphorous content of 12 wt. % to 15 wt. %, and wherein the first coating layer has coated directly thereon a second hard coating layer overlaying the leading edges of the plurality of blades, wherein the second hard coating layer has a hardness of greater than about 800 HV and comprises a material chosen from the group of carbides, nitrides, diamond like carbon (DLC), or combinations thereof, wherein the leading edges are positioned longitudinally forward from the trailing edges of the plurality of blades along the rotational axis with respect to a flow of air along the wheel when the wheel is rotating, and wherein the second hard coating layer has a thickness along the leading edges of from about 1 to about 10 microns and the thickness reduces in a gradually tapering manner rearward towards the trailing edges such that the thickness of the second hard coating layer is zero microns at or longitudinally forward of the trailing edges of the plurality of blades.

13. A method for making a wheel, the method comprising: providing a substrate wheel that comprises: a hub portion configured to rotate about a rotational axis, and a plurality of blades extending radially outward from the hub portion, wherein each blade of the plurality of blades comprises a leading edge and a trailing edge, wherein the hub portion and the plurality of blades comprise a substrate metal that comprises aluminum or an alloy thereof; forming on the substrate metal of the hub portion and the plurality of blades a first coating layer comprising electroless nickel-phosphorous that comprises a phosphorous content of 12 wt. % to 15 wt. %, wherein forming the first coating layer comprises immersing the substrate wheel in an electroless nickel-phosphorous plating bath comprising nickel cations and phosphorous oxide anions and subsequently, exposing the substrate wheel including the first coating layer to a heat treatment process to thereby increase adhesion strength of the first coating layer to the substrate metal; and forming a second hard coating layer from a physical vapor deposition (PVD)-compatible material on the first coating layer overlying the leading edges of the plurality of blades, wherein forming the second hard coating layer comprises depositing the PVD-compatible material at a process deposition temperature 250° C. or less, and wherein the second hard coating layer has a thickness that is greatest at the leading edges and that decreases rearward in a gradually tapering manner such that the thickness is zero microns at or longitudinally forward of the trailing edges of the plurality of blades.

14. The method of claim 13, wherein exposing the substrate wheel to the heat treatment process includes exposing the substrate wheel including the first coating layer to a temperature of from about 100° C. to about 150° C. for a time of from about 1 to about 4 hours.

15. The method of claim 13, wherein forming the second hard coating layer comprises forming the second hard coating layer using a PVD process that includes processing conditions including a process deposition temperature, and wherein forming the second hard coating comprises depositing the PVD-compatible material on the first coating layer at the process deposition temperature of about 250° C. or less.
16. The method of claim 15, wherein forming the second hard coating comprises depositing the PVD-compatible material on the first coating layer at the process deposition temperature of from about 70° C. to about 250° C.
17. The method of claim 13, wherein the leading edges are positioned longitudinally forward from the trailing edges of the plurality of blades along the rotational axis with respect to a flow of air along the wheel when the wheel is rotating, and wherein forming the second hard coating comprises forming the second hard coating layer having a thickness that is greatest at the leading edges and that decreases rearward towards the trailing edges.
18. The method of claim 17, wherein forming the second hard coating comprises forming the second hard coating layer such that the thickness of the second hard coating layer reduces in a gradually tapering manner rearward towards the trailing edges of the plurality of blades and is zero microns at or longitudinally forward of the trailing edges of the plurality of blades.
19. The method of claim 13, wherein forming the second hard coating comprises forming the second hard coating having a hardness of from about 1,000 HV to about 3,500 HV.
-