

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250281947

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

KIM; Myung Kyu

DEPOSITING APPARATUS AND CLEANING METHOD OF THE SAME

Abstract

A depositing apparatus includes a deposition source including at least one deposition nozzle that spray a deposition material, a spray angle limiting portion spaced apart from the deposition source and limiting a spray angle of the deposition material sprayed from the at least one deposition nozzle, and a cleaning module disposed between the deposition source and the spray angle limiting portion and heating the deposition material accumulated on the spraying angle limiting portion.

Inventors: KIM; Myung Kyu (Yongin-si, KR)

Applicant: Samsung Display Co., LTD. (Yongin-si, KR)

Family ID: 1000008292392

Assignee: Samsung Display Co., LTD. (Yongin-si, KR)

Appl. No.: 18/953505

Filed: November 20, 2024

Foreign Application Priority Data

KR 10-2024-0031995

Mar. 06, 2024

Publication Classification

Int. Cl.: B08B7/00 (20060101); B08B9/027 (20060101); C23C14/24 (20060101)

U.S. Cl.:

CPC B08B7/0071 (20130101); B08B9/027 (20130101); C23C14/24 (20130101); B08B2209/027 (20130101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

[0001] This application claims priority to and benefits of Korean Patent Application No. 10-2024-0031995 under 35 U.S.C. § 119, filed on Mar. 6, 2024, in the Korean Intellectual Property Office (KIPO), the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Technical Field

[0002] The disclosure relates to a depositing apparatus and a cleaning method of the same.

2. Description of the Related Art

[0003] An organic light emitting display device is a display device using a phenomenon in which electrons injected from a cathode and holes injected from an anode recombine in an organic thin film to form excitons, and light of a specific wavelength is generated by energy from the formed excitons.

[0004] As a method of depositing organic materials or metals used as electrodes in the organic light emitting display device, a vacuum deposition method using a depositing apparatus may be used. The vacuum deposition method may be performed by positioning a substrate on which an organic thin film is to be formed inside a vacuum chamber, making a deposition mask having the same pattern as a pattern of the thin film to be formed in close contact with the substrate, and depositing a deposition material on the substrate by evaporating or sublimating the deposition material such as an organic material using a deposition source.

[0005] A spray angle limiting portion for limiting a spray angle of a deposition material sprayed from a deposition nozzle of the deposition source may be disposed in the deposition apparatus in which the vacuum deposition method is performed. During the process of depositing the deposition material, as the deposition material accumulates in the spray angle limiting portion, the spray angle of the deposition material sprayed from the deposition nozzle may change. In addition, the deposition material accumulated on the spray angle limiting portion may fall and thus close the deposition nozzle.

SUMMARY

[0006] Aspects of the disclosure provide a depositing apparatus capable of preventing a spray angle of a deposition material from changing by preventing the deposition material from being accumulated on a spray angle limiting portion, and ensuring continuous operation of a deposition process by cleaning the deposition material that closes a deposition nozzle, and a cleaning method of the same.

[0007] However, embodiments of the disclosure are not limited to those set forth herein. The above and other embodiments of the disclosure will become more apparent to one of ordinary skill in the art to which the disclosure pertains by referencing the detailed description of the disclosure given below.

[0008] According to an embodiment of the disclosure, a depositing apparatus may include a deposition source including at least one deposition nozzle that sprays a deposition material, a spray angle limiting portion spaced apart from the deposition source and limiting a spray angle of the deposition material sprayed from the at least one deposition nozzle, and a cleaning module disposed between the deposition source and the spray angle limiting portion and heating the deposition material accumulated on the spraying angle limiting portion.

[0009] The cleaning module may be disposed closer to the spray angle limiting portion than the deposition source.

[0010] The at least one deposition nozzle may include a plurality of deposition nozzles, the plurality of deposition nozzles may be arranged in a first direction, and the cleaning module may be

disposed to be movable in the first direction.

[0011] The spray angle limiting portion may include an extension plate extending to an upper direction from the deposition source, and a blocking plate extending from the extension plate in a second direction and forming an open area through which the deposition material passes.

[0012] The second direction may be a direction horizontally orthogonal to the first direction.

[0013] The open area may be disposed above the plurality of deposition nozzles and extend in the first direction.

[0014] The cleaning module may include, a moving rail extending in the first direction below the blocking plate, a moving block disposed on the moving rail and moving along the moving rail, and a heating member extending from the moving block in the second direction.

[0015] The cleaning module may further include a first driver connecting the moving block and the heating member and moving the heating member in the second direction.

[0016] The cleaning module may further include a second driver connecting the first driver and the heating member and rotating the heating member so that an extended end of the heating member faces a third direction.

[0017] The third direction may be a direction vertically orthogonal to the first direction and the second direction.

[0018] The cleaning module may further include a third driver connecting the second driver and the heating member and moving the heating member in the third direction.

[0019] The heating member may be moved by the third driver and inserted into one of the plurality of deposition nozzles.

[0020] The extension plate may include a plurality of extension plates, the plurality of extension plates may include a first extension plate and a second extension plate, the first extension plate may extend in an upper direction from a side of the deposition source, and the second extension plate may extend in an upper direction from another side of the deposition source so that the plurality of deposition nozzles are disposed between the first extension plate and the second extension plate.

[0021] The blocking plate may include a plurality of blocking plates, the plurality of blocking plates may include a first blocking plate and a second blocking plate, the first blocking plate may extend from the first extension plate in the second direction so as to be directed to an upper side of the plurality of deposition nozzles, the second blocking plate may extend from the second extension plate in the second direction to face the first blocking plate, and an extended end of the first blocking plate and an extended end of the second blocking plate may be spaced apart from each other, so that the open area is formed between the first blocking plate and the second blocking plate.

[0022] The cleaning module may include a plurality of cleaning modules, the plurality of cleaning modules may include a first cleaning module and a second cleaning module, the first cleaning module may be disposed below the first blocking plate, and the second cleaning module may be disposed below the second blocking plate.

[0023] According to an embodiment of the disclosure, a cleaning method of a depositing apparatus may include cleaning a spray angle limiting portion including moving a cleaning module disposed below the spray angle limiting portion that limits a spray angle of a deposition material sprayed from a deposition nozzle along the spray angle limiting portion, and removing the deposition material accumulated on the spray angle limiting portion by a heating member of the cleaning module, and cleaning the deposition nozzle including inserting the heating member into the deposition nozzle to remove the deposition material accumulated in the deposition nozzle.

[0024] The deposition nozzle may include a plurality of deposition nozzles arranged in a first direction, the spray angle limiting portion may include a blocking plate that forms an open area through which the deposition material passes extending in the first direction above the plurality of deposition nozzles, and the cleaning of the spray angle limiting portion may include moving the cleaning module in the first direction below the blocking plate.

[0025] The cleaning module may further include, a moving rail extending in the first direction below the blocking plate, and a moving block supporting the heating member and disposed on the moving rail to move along the moving rail, and the cleaning of the spray angle limiting portion may include moving the moving block along the moving rail.

[0026] The cleaning module may further include, a first driver moving the heating member in a second direction horizontally orthogonal to the first direction and positioning the heating member above the plurality of deposition nozzles, a second driver rotating the heating member to a third direction vertically orthogonal to the first direction and the second direction so that the heating member faces the plurality of deposition nozzles, and a third driver moving the heating member in the third direction so that the heating member is inserted into one of the plurality of deposition nozzles. The cleaning of the deposition nozzle may further include, moving the heating member in the second direction by the first driver and positioning the heating member above the plurality of deposition nozzles, rotating the heating member positioned above the one of the plurality of deposition nozzles by the second driver to face the one of the plurality of deposition nozzles, and inserting the heating member rotated to face the one of the plurality of deposition nozzles into the one of the plurality of deposition nozzles by the third driver.

[0027] The cleaning of the deposition nozzle may further include, moving the heating member inserted into the one of the plurality of deposition nozzles in the third direction by the third driver so that the heating member is pulled out from the one of the plurality of deposition nozzles, moving the moving block along the moving rail so that the heating member pulled out from the one of the plurality of deposition nozzles is positioned above another one of the plurality of deposition nozzles adjacent to the one of the plurality of deposition nozzles, and inserting the heating member positioned above the another one of the plurality of deposition nozzles into the another one of the plurality of deposition nozzles by the third driver.

[0028] According to the depositing apparatus and the cleaning method of the same according to the disclosure, it is possible to prevent the spray angle of the deposition material from changing by preventing the deposition material from being accumulated on the spray angle limiting portion, and to ensure continuous operation of the deposition process by cleaning the deposition material that closes the deposition nozzle.

[0029] The effects according to the embodiments of the disclosure are not limited to those mentioned above and more various effects are included in the following description of the disclosure.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0030] The above and other aspects and features of the disclosure will become more apparent by describing in detail embodiments thereof with reference to the attached drawings, in which:

[0031] FIG. 1 is a schematic cross-sectional view illustrating a depositing apparatus according to an embodiment of the disclosure;

[0032] FIG. 2 is a plan view illustrating a deposition source, a spray angle limiting portion, and a cleaning module of FIG. 1;

[0033] FIG. 3 is a left side view of FIG. 2;

[0034] FIG. 4 is a right side view of FIG. 2;

[0035] FIG. 5 is a schematic cross-sectional view illustrating a state in which a first driver is driven in the front view of FIG. 2;

[0036] FIG. 6 is a schematic cross-sectional view illustrating a state in which a second driver is driven in FIG. 5;

[0037] FIG. 7 is a schematic cross-sectional view illustrating a state in which a third driver is

driven in FIG. 6;

[0038] FIG. 8 is a schematic cross-sectional view illustrating a state in which a spray angle of a deposition nozzle is changed due to a deposition material accumulated on the spray angle limiting portion of FIG. 1;

[0039] FIG. 9 is a plan view illustrating a state in which a first cleaning module and a second cleaning module in FIG. 2 are moved in a first direction;

[0040] FIG. 10 is a schematic cross-sectional view illustrating a state in which a heating member is moved in a second direction by the first driver in the front view of FIG. 2;

[0041] FIG. 11 is a schematic cross-sectional view illustrating a state in which the heating member is rotated to face a third direction by the second driver in FIG. 10;

[0042] FIG. 12 is a schematic cross-sectional view illustrating a state in which the heating member is moved in the third direction by the third driver in FIG. 11 and inserted into a deposition nozzle;

[0043] FIG. 13 is a schematic cross-sectional view illustrating a state in which the heating member is moved in the third direction by the third driver in FIG. 12 and pulled out from the deposition nozzle;

[0044] FIG. 14 is a schematic cross-sectional view illustrating a state in which a first moving block is moved in the first direction along a first moving rail in the left side view of FIG. 13; and

[0045] FIG. 15 is a schematic cross-sectional view illustrating a state in which the heating member is moved in the third direction by the third driver in FIG. 14 and inserted into another deposition nozzle.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0046] Advantages and features of the disclosure and methods to achieve them will become apparent from the descriptions of embodiments hereinbelow with reference to the accompanying drawings. However, the disclosure is not limited to embodiments disclosed herein but may be implemented in various different ways. The embodiments are provided for making the disclosure of the disclosure thorough and for fully conveying the scope of the disclosure to those skilled in the art. It is to be noted that the scope of the disclosure is defined only by the claims.

[0047] When an element, such as a layer, is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being “directly on,” “directly connected to,” or “directly coupled to” another element or layer, there are no intervening elements or layers present. To this end, the term “connected” may refer to physical, electrical, and/or fluid connection, with or without intervening elements. Also, when an element is referred to as being “in contact” or “contacted” or the like to another element, the element may be in “electrical contact” or in “physical contact” with another element; or in “indirect contact” or in “direct contact” with another element. Like reference numerals denote like elements throughout the descriptions.

[0048] The use of cross-hatching and/or shading in the accompanying drawings is generally provided to clarify boundaries between adjacent elements. As such, neither the presence nor the absence of cross-hatching or shading conveys or indicates any preference or requirement for particular materials, material properties, dimensions, proportions, commonalities between illustrated elements, and/or any other characteristic, attribute, property, etc., of the elements, unless specified. Further, in the accompanying drawings, the size and relative sizes of elements may be exaggerated for clarity and/or descriptive purposes. When an embodiment may be implemented differently, a specific process order may be performed differently from the described order. For example, two consecutively described processes may be performed substantially at the same time or performed in an order opposite to the described order.

[0049] Although terms such as first, second, etc. are used to distinguish arbitrarily between the elements such terms describe, and thus these terms are not necessarily intended to indicate temporal or other prioritization of such elements. These terms are used to merely distinguish one

element from another. Accordingly, as used herein, a first element may be a second element within the technical scope of the disclosure.

[0050] Spatially relative terms, such as “beneath,” “below,” “under,” “lower,” “above,” “upper,” “over,” “higher,” “side” (e.g., as in “sidewall”), and the like, may be used herein for descriptive purposes, and, thereby, to describe one elements relationship to another element(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. Furthermore, the apparatus may be otherwise oriented (e.g., rotated 90 degrees or at other orientations), and, as such, the spatially relative descriptors used herein interpreted accordingly.

[0051] Features of various embodiments of the disclosure may be combined partially or totally. As will be clearly appreciated by those skilled in the art, technically various interactions and operations are possible. Various embodiments can be practiced individually or in combination.

[0052] Unless otherwise defined or implied herein, all terms (including technical and scientific terms) used have the same meaning as commonly understood by those skilled in the art to which this disclosure pertains. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and should not be interpreted in an ideal or excessively formal sense unless clearly defined in the specification.

[0053] Hereinafter, embodiments will be described with reference to the accompanying drawings.

[0054] FIG. 1 is a schematic cross-sectional view illustrating a depositing apparatus **10** according to an embodiment of the disclosure. FIG. 2 is a plan view illustrating a deposition source **400**, a spray angle limiting portion, and a cleaning module of FIG. 1. FIG. 3 is a left side view of FIG. 2. FIG. 4 is a right side view of FIG. 2.

[0055] Referring to FIGS. 1 to 4, the depositing apparatus **10** according to an embodiment of the disclosure may deposit an organic material or a metal used as an electrode on a substrate S. The depositing apparatus **10** may include a chamber **100**, a substrate holder **200**, a mask assembly **300**, a deposition source **400**, a spray angle limiting portion, and a cleaning module.

[0056] The chamber **100** may provide a space in which a deposition process is performed. The interior of the chamber **100** may be maintained in a vacuum while performing the deposition process. Maintaining the interior of the chamber **100** in a vacuum may mean maintaining a pressure inside the chamber **100** at a low pressure. The chamber **100** may include a port (not illustrated) for porting in and out of the substrate S. The chamber **100** may further include a vacuum pump (not illustrated) for controlling the pressure inside the chamber **100** and exhausting the deposition material not deposited on the substrate S, and an exhaust port (not illustrated) connected to the vacuum pump.

[0057] The substrate S on which the organic material or the metal used as the electrode is deposited may be provided as an insulating substrate, a semiconductor substrate, a display substrate, etc., but is not limited thereto. In the disclosure, a substrate S used in an organic light emitting display device will be described as an embodiment. A structure may be formed on the substrate S through a deposition process. Depending on a process of manufacturing an organic light emitting display device, the structure formed on the substrate S through the deposition process may be formed in various ways. For example, in a process of forming a hole injection layer, a pixel defining film and an anode electrode may be formed on the substrate S. In a process of forming an organic light emitting layer, a hole injection layer and a hole transport layer as well as a pixel defining layer and an anode electrode may be formed on the substrate S.

[0058] The substrate holder **200** may support the substrate S. The substrate holder **200** may be disposed inside the chamber **100**. In an embodiment, the substrate holder **200** may be disposed on

an upper side inside the chamber **100**, and the substrate S may be seated on a lower portion of the substrate holder **200** and supported by the substrate holder **200**. The substrate holder **200** may include a fixing member (not illustrated). The fixing member may assist in fixing the substrate S and the mask assembly **300**, and may serve to maintain a constant distance between the substrate S and the mask assembly **300**. The fixing member may be provided as a frame structure that may be separately mounted.

[0059] The mask assembly **300** may define an area where the deposition material sprayed from the deposition source **400** is deposited on the substrate S. The mask assembly **300** may include a mask portion **310**, a transmission portion **320**, and a mask side wall portion (not illustrated). The mask portion **310** may cover a partial area of the substrate S to prevent the deposition material sprayed from the deposition source **400** from being deposited on the corresponding area. The transmission portion **320**, which is an area that exposes a partial area of the substrate S, may be an open area formed between the mask portions **310**. The deposition material may be sprayed onto an exposed area of the substrate S exposed by the transmission portion **320** and deposited on the exposed area of the substrate S. Therefore, the deposition material sprayed from the deposition source **400** may be deposited on the substrate S while forming a pattern through the mask assembly **300**. The mask side wall portion may be positioned in an edge area of the mask assembly **300** to prevent the deposition material from spreading to areas other than the substrate S. The mask assembly **300** may be a raw mask such as a fine metal mask (FMM) or multiple segmented masks, but is not limited thereto. The mask assembly **300** may be disposed close to and fixed to the substrate S, and a distance between the mask assembly **300** and the substrate S may be adjusted by the substrate holder **200** and the fixing member.

[0060] The deposition source **400** may provide a deposition material to be deposited on the substrate S. The deposition source **400** may be disposed inside the chamber **100**, and may be disposed to face the substrate S. In an embodiment, in case that the substrate holder **200** on which the substrate S is seated is disposed on an upper side inside the chamber **100**, the deposition source **400** may be disposed on a lower side inside the chamber **100**. The deposition source **400** may include a base plate **410**, a deposition nozzle supporter **420**, and a deposition nozzle **430**.

[0061] The base plate **410** may support at least one of the deposition nozzle supporter **420** and the deposition nozzle **430**. The base plate **410** may be disposed on a lower side inside the chamber **100**. The base plate **410** may be provided as a plate with a thickness, may be disposed so that a lower surface is in contact with an inner lower surface of the chamber **100**, and may have the deposition nozzle supporter **420** disposed on an upper surface to support the deposition nozzle supporter **420**.

[0062] The deposition nozzle supporter **420** may support the deposition nozzle **430**. The deposition nozzle supporter **420** may be disposed on the upper surface of the base plate **410** and supported by the base plate **410**. The deposition nozzle supporter **420** may be provided as a block having a thickness and may be formed on the upper surface of the base plate **410** to extend in a first direction DR1.

[0063] The deposition nozzle **430** may spray the deposition material and supply the deposition material to the substrate S. The deposition nozzle **430** may be disposed on the upper surface of the deposition nozzle supporter **420** and supported by the deposition nozzle supporter **420**. Multiple deposition nozzles **430** may be provided and arranged to be spaced apart from each other along the first direction DR1 on the upper surface of the deposition nozzle supporter **420**. The deposition nozzle **430** may be connected to a deposition material storage unit (not illustrated) and may spray the deposition material stored in the deposition material storage unit. The deposition nozzle **430** may supply the deposition material to the substrate S by spraying the deposition material in an upper direction. In other words, the deposition nozzle **430** may spray the deposition material to an upper side in a third direction DR3. A spray passage **431** may be formed in the center of the deposition nozzle **430**, and the deposition material may be sprayed through the spray passage **431**.

[0064] The spray angle limiting portion may be disposed to be spaced apart from the deposition

source **400** to limit a spray angle of the deposition material sprayed from the deposition nozzle **430**. The spray angle limiting portion may adjust the area and thickness where the deposition material is deposited by limiting the spray angle of the deposition material sprayed from the deposition nozzle **430**. Multiple spray angle limiting portions may be provided. The spray angle limiting portions may include a first spray angle limiting portion **500** and a second spray angle limiting portion **600**. [0065] The first spray angle limiting portion **500** may be disposed on the left side (left side in FIG. **1**) of the deposition source **400** in a second direction DR2 and block a portion of the deposition material sprayed from the deposition nozzle **430**, thereby adjusting the spray angle of the deposition material. The first spray angle limiting portion **500** may include a first extension plate **510** and a first blocking plate **520**. The second direction DR2 may be defined as a direction horizontally orthogonal to the first direction DR1.

[0066] The first extension plate **510** may extend in an upper direction from the base plate **410** and may support the first blocking plate **520**. The first extension plate **510** may be disposed on the left side (left side in FIG. **1**) of the deposition nozzle **430**. The first extension plate **510** may be provided as a plate having a thickness and may extend along the first direction DR1 on the upper surface of the base plate **410**. An extended length of the first extension plate **510** may correspond to an extended length of the deposition nozzle supporter **420**.

[0067] The first blocking plate **520** may extend from an upper end of the first extension plate **510** to the right side (right side in FIG. **1**) in the second direction DR2 and may block a portion of the deposition material sprayed from the deposition nozzle **430**. The first blocking plate **520** may be provided as a plate having a thickness and may extend from the upper end of the first extension plate **510** along the first direction DR1. An extended length of the first blocking plate **520** may correspond to an extended length of the deposition nozzle supporter **420**.

[0068] The second spray angle limiting portion **600** may be disposed on the right side (right side in FIG. **2**) of the deposition source **400** in the second direction DR2 and block a portion of the deposition material sprayed from the deposition nozzle **430**, thereby adjusting the spray angle of the deposition material. The second spray angle limiting portion **600** may include a second extension plate **610** and a second blocking plate **620**.

[0069] The second extension plate **610** may extend in an upper direction from the base plate **410** and may support the second blocking plate **620**. The second extension plate **610** may be disposed on the right side (right side in FIG. **1**) of the deposition nozzle **430**. The second extension plate **610** may be provided as a plate having a thickness and may extend along the first direction DR1 on the upper surface of the base plate **410**. An extended length of the second extension plate **610** may correspond to an extended length of the deposition nozzle supporter **420**.

[0070] The second blocking plate **620** may extend from an upper end of the second extension plate **610** to the left side (left side in FIG. **1**) in the second direction DR2 and may block a portion of the deposition material sprayed from the deposition nozzle **430**. The second blocking plate **620** may be provided as a plate having a thickness and may extend from the upper end of the second extension plate **610** along the first direction DR1. An extended length of the second blocking plate **620** may correspond to an extended length of the deposition nozzle supporter **420**. An end of the second blocking plate **620** in the second direction DR2 may be spaced apart from an end of the first blocking plate **520** in the second direction DR2. In other words, as the end of the first blocking plate **520** in the second direction DR2 and the end of the second blocking plate **620** in the second direction DR2 are spaced apart from each other, an open area O may be formed between the first blocking plate **520** and the second blocking plate **620**. The open area O may be an area through which the deposition material passes. As a portion of the deposition material is blocked by the first blocking plate **520** and the second blocking plate **620** and the deposition material passes through the open area O, a spray angle α of the deposition material sprayed from the deposition nozzle **430** may be limited. The spray angle α of the deposition material may be changed by adjusting the extended length of the first extension plate **510** and the second extension plate **610** in the third

direction DR3, or adjusting the extended length of the first blocking plate **520** and the second blocking plate **620** in the second direction DR2. The open area O may be disposed above the deposition nozzle **430** and may extend along the first direction DR1.

[0071] FIG. 5 is a schematic cross-sectional view illustrating a state in which a first driver is driven in the front view of FIG. 2. FIG. 6 is a schematic cross-sectional view illustrating a state in which a second driver is driven in FIG. 5. FIG. 7 is a schematic cross-sectional view illustrating a state in which a third driver is driven in FIG. 6.

[0072] Referring further to FIGS. 5 to 7, the cleaning module may be disposed to be movable along the spray angle limiting portion between the deposition source **400** and the spray angle limiting portion. The cleaning module may be disposed close to the spray angle limiting portion and move along the spray angle limiting portion, thereby removing the deposition material accumulated on the spray angle limiting portion. The cleaning module may be disposed to be movable in the first direction DR1. Multiple cleaning modules may be provided. The cleaning modules may include a first cleaning module **700** and a second cleaning module **800**.

[0073] The first cleaning module **700** may remove the deposition material accumulated on the first blocking plate **520**. The first cleaning module **700** may remove the deposition material accumulated in the spray passage **431** of the deposition nozzle **430**. The first cleaning module **700** may be disposed below the first blocking plate **520**. The first cleaning module **700** may include a first moving rail **710**, a first moving block **720**, a first heating member **730**, a first driver **740**, a second driver **750**, and a third driver **760**.

[0074] The first moving rail **710** may provide a path along which the first moving block **720** moves. The first moving rail **710** may be disposed below the first blocking plate **520** to be spaced apart from the first blocking plate **520** by a distance. The first moving rail **710** may extend in the first direction DR1 along the first blocking plate **520**. In other words, the first moving rail **710** may extend from a side (lower side in FIG. 2) of the first blocking plate **520** in the first direction DR1 to another side (upper side in FIG. 2) of the first blocking plate **520** in the first direction DR1. An extended length of the first moving rail **710** may be less than the extended length of the first blocking plate **520** in the first direction DR1.

[0075] The first moving block **720** may move along the first moving rail **710**. The first moving block **720** may be disposed on the first moving rail **710** between the first moving rail **710** and the first blocking plate **520**. A moving driver (not illustrated) may be disposed inside the first moving block **720**, so that the first moving block **720** may be moved along the first moving rail **710** according to a driving of the moving driver. Since the first moving block **720** moves along the first moving rail **710**, the first moving block **720** may be moved in the first direction DR1.

[0076] The first heating member **730** may be supported by the first moving block **720** and movable in the first direction DR1 along the first moving block **720**. The first heating member **730** may extend from the first moving block **720** to the right side (right side in FIG. 2) in the second direction DR2. The first heating member **730** may extend so that an extended end of first heating member **730** is in contact with a same virtual vertical surface as the extended end of the first blocking plate **520**. The first heating member **730** may be heated by an induction heating method or may be provided as a cartridge heater, etc., but is not limited thereto. The first heating member **730** may be movable in the first direction DR1 as the first moving block **720** moves along the first moving rail **710**, and may be in contact with the deposition material accumulated on the first blocking plate **520**. Accordingly, the first heating member **730** may heat the deposition material accumulated on the first blocking plate **520** to vaporize and remove the deposition material. In this way, as the first heating member **730** removes the deposition material accumulated on the first blocking plate **520**, the first blocking plate **520** may be cleaned.

[0077] The first driver **740** may move the first heating member **730** in the second direction DR2. The first driver **740** may connect the first moving block **720** and the first heating member **730** to each other. The first driver **740** may include multiple stages having different diameters. The first

driver **740** may be formed in a state in which a stage having a smaller diameter is inserted into a stage having an arbitrary diameter. For example, the first driver **740** may include a first stage and a second stage, and may be formed in a state in which the second stage is inserted into the first stage. The first stage may be connected to the first moving block **720**, and the second stage may be connected to the second driver **750**. A separate actuator (not illustrated) may be disposed inside the first driver **740**, so that the second stage may be pulled into the interior of the first stage or may be pulled out of the first stage by driving the actuator. The first driver **740** may be disposed inside the first moving block **720**. In case that the first driver **740** is disposed inside the first moving block **720**, the first heating member **730** may be disposed to be in contact with the first moving block **720**. In case that the first stage is moved from the first moving block **720** to the right side (right side in FIG. 5) in the second direction DR2 and the second stage is pulled out from the first stage to the right side in the second direction DR2 by driving the actuator of the first driver **740**, the first heating member **730** may be moved from the first moving block **720** to the right side in the second direction DR2.

[0078] The second driver **750** may rotate the first heating member **730** so that the extended end of the first heating member **730** is directed to a third direction DR3. The second driver **750** may connect the first driver **740** and the third driver **760** to each other. The second driver **750** may be connected to the second stage of the first driver **740** by a rotation shaft and rotated around a rotation axis. By rotating the second driver **750**, the extended end of the first heating member **730** may be rotated to face a lower side (lower side in FIG. 6) in the third direction DR3. In other words, the extended end of the first heating member **730** may be rotated to face the deposition nozzle **430** by driving the second driver **750**. A separate rotation motor (not illustrated) may be connected to the rotation shaft, so that the second driver **750** may be rotated by driving the rotation motor. The third direction DR3 may be defined as a direction vertically orthogonal to the first and second directions DR1 and DR2.

[0079] The third driver **760** may move the first heating member **730** in the third direction DR3. The third driver **760** may connect the second driver **750** and the first heating member **730** to each other. The third driver **760** may be disposed inside the second driver **750**. A separate actuator (not illustrated) may be disposed inside the third driver **760**, so that the third driver **760** may be pulled out from the inside of the second driver **750** by driving the actuator. In case that the third driver **760** is disposed inside the second driver **750**, the first heating member **730** may be disposed to be in contact with the second driver **750**. In case that the actuator of the third driver **760** is driven and the third driver **760** is pulled out from the second driver **750** toward the lower side (lower side in FIG. 7) in the third direction DR3, the first heating member **730** may be moved to the lower side in the third direction DR3 from the second driver **750** and inserted into the spray passage **431** of the deposition nozzle **430**. In this way, as the first heating member **730** is inserted into the spray passage **431** of the deposition nozzle **430**, the deposition material accumulated in the spray passage **431** of the deposition nozzle **430** may be heated to vaporize and remove the deposition material.

[0080] The second cleaning module **800** may remove the deposition material accumulated on the second blocking plate **620**. The second cleaning module **800** may be disposed below the second blocking plate **620**. The second cleaning module **800** may include a second moving rail **810**, a second moving block **820**, and a second heating member **830**.

[0081] The second moving rail **810** may provide a path along which the second moving block **820** moves. The second moving rail **810** may be disposed below the second blocking plate **620** to be spaced apart from the second blocking plate **620** by a distance. The second moving rail **810** may extend in the first direction DR1 along the second blocking plate **620**. In other words, the second moving rail **810** may extend from a side (lower side in FIG. 2) of the second blocking plate **620** in the first direction DR1 to another side (upper side in FIG. 2) of the second blocking plate **620** in the first direction DR1. An extended length of the second moving rail **810** may be less than the extended length of the second blocking plate **620** in the first direction DR1.

[0082] The second moving block **820** may move along the second moving rail **810**. The second moving block **820** may be disposed on the second moving rail **810** between the second moving rail **810** and the second blocking plate **620**. A moving driver (not illustrated) may be disposed inside the second moving block **820**, so that the second moving block **820** may be moved along the second moving rail **810** according to a driving of the moving driver. Since the second moving block **820** moves along the second moving rail **810**, the second moving block **820** may be moved in the first direction **DR1**.

[0083] The second heating member **830** may be supported by the second moving block **820** and movable in the first direction **DR1** along the second moving block **820**. The second heating member **830** may extend from the second moving block **820** to the left side (left side in FIG. 2) in the second direction **DR2**. The second heating member **830** may extend so that an extended end of the second heating member **830** is in contact with a same virtual vertical surface as the extended end of the second blocking plate **620**. The second heating member **830** may be heated by an induction heating method or may be provided as a cartridge heater, etc., but is not limited thereto. The second heating member **830** may be movable in the first direction **DR1** as the second moving block **820** moves along the second moving rail **810**, and may be in contact with the deposition material accumulated on the second blocking plate **620**. Accordingly, the second heating member **830** may heat the deposition material accumulated on the second blocking plate **620** to vaporize and remove the deposition material. In this way, as the second heating member **830** removes the deposition material accumulated on the second blocking plate **620**, the second blocking plate **620** may be cleaned.

[0084] Hereinafter, a cleaning method of a depositing apparatus according to an embodiment of the disclosure will be described with reference to the accompanying drawings.

[0085] FIG. 8 is a schematic cross-sectional view illustrating a state in which a spray angle of a deposition nozzle is changed due to a deposition material accumulated on the spray angle limiting portion of FIG. 1.

[0086] Referring to FIG. 8, as the usage time of the depositing apparatus **10** elapses, the deposition material sprayed from the deposition nozzle **430** may accumulate on a lower portion of the first blocking plate **520** of the first spray angle limiting portion **500** and a lower portion of the second blocking plate **620** of the second spray angle limiting portion **600**. A spray angle β of the deposition nozzle **430** may be reduced by the deposition material **M** accumulated on the lower portion of the first blocking plate **520** and the lower portion of the second blocking plate **620**. If the spray angle β of the deposition nozzle **430** is reduced, the area and deposition thickness where the deposition material is deposited on the substrate **S** may change, which may cause defects in the organic light emitting display device. As the deposition material **M** accumulated on the lower portion of the first blocking plate **520** and the lower portion of the second blocking plate **620** may fall to the deposition nozzle **430**, the spray passage **431** of the deposition nozzle **430** may be closed. Since the defects in the organic light emitting display device may be caused by the deposition material **M** accumulated on the lower portion of the first blocking plate **520** and the lower portion of the second blocking plate **620** and the deposition material accumulated in the spray passage **431** of the deposition nozzle **430**, there is a need to remove the deposition material **M** accumulated on the first blocking plate **520**, the second blocking plate **620**, and the deposition nozzle **430**.

[0087] The cleaning method of the depositing apparatus according to an embodiment of the disclosure may include a spray angle limiting portion cleaning step and a deposition nozzle cleaning step.

[0088] FIG. 9 is a plan view illustrating a state in which a first cleaning module and a second cleaning module in FIG. 2 are moved in a first direction.

[0089] Referring to FIG. 9, the spray angle limiting portion cleaning step may be a step in which the first cleaning module **700** and the second cleaning module **800** are moved in the first direction **DR1** along the first spray angle limiting portion **500** and the second spray angle limiting portion

600 below the first spray angle limiting portion **500** and the second spray angle limiting portion **600**.

[0090] In the spray angle limiting portion cleaning step, as the first moving block **720** of the first cleaning module **700** is moved in the first direction DR1 along the first moving rail **710**, the first heating member **730** may be moved in the first direction DR1 below the first blocking plate **520**. The first heating member **730** may be moved below the first blocking plate **520** and be in contact with the deposition material M accumulated on the lower side of the first blocking plate **520**. The first heating member **730** in contact with the deposition material M accumulated on the lower side of the first blocking plate **520** may vaporize the deposition material M accumulated on the lower side of the first blocking plate **520** and remove the deposition material M from the first blocking plate **520**, thereby clean the first blocking plate **520**. The first moving block **720** may be reciprocated from a side (lower side in FIG. 9) of the first moving rail **710** to another side (upper side in FIG. 9) of the first moving rail **710** to reciprocate the first heating member **730** in the first direction DR1 below the first blocking plate **520**.

[0091] In the spray angle limiting portion cleaning step, as the second moving block **820** of the second cleaning module **800** is moved in the first direction DR1 along the second moving rail **810**, the second heating member **830** may be moved in the first direction DR1 below the second blocking plate **620**. The second heating member **830** may be moved below the second blocking plate **620** and be in contact with the deposition material M accumulated on the lower side of the second blocking plate **620**. The second heating member **830** in contact with the deposition material M accumulated on the lower side of the second blocking plate **620** may vaporize the deposition material M accumulated on the lower side of the second blocking plate **620** and remove the deposition material M from the second blocking plate **620**, thereby clean the second blocking plate **620**. The second moving block **820** may be reciprocated from a side (lower side in FIG. 9) of the second moving rail **810** to another side (upper side in FIG. 9) of the second moving rail **810** to reciprocate the second heating member **830** in the first direction DR1 below the second blocking plate **620**.

[0092] In the spray angle limiting portion cleaning step, the first cleaning module **700** and the second cleaning module **800** may be moved separately or may be moved equally in parallel positions, but are not limited thereto.

[0093] FIG. 10 is a schematic cross-sectional view illustrating a state in which a heating member is moved in a second direction by the first driver in the front view of FIG. 2. FIG. 11 is a schematic cross-sectional view illustrating a state in which the heating member is rotated to face a third direction by the second driver in FIG. 10. FIG. 12 is a schematic cross-sectional view illustrating a state in which the heating member is moved in the third direction by the third driver in FIG. 11 and inserted into a deposition nozzle. FIG. 13 is a schematic cross-sectional view illustrating a state in which the heating member is moved in the third direction by the third driver in FIG. 12 and pulled out from the deposition nozzle. FIG. 14 is a schematic cross-sectional view illustrating a state in which a first moving block is moved in the first direction along a first moving rail in the left side view of FIG. 13. FIG. 15 is a schematic cross-sectional view illustrating a state in which the heating member is moved in the third direction by the third driver in FIG. 14 and inserted into another deposition nozzle.

[0094] Referring to FIGS. 10 to 15, the deposition nozzle cleaning step may be a step in which the first heating member **730** is inserted into the spray passage **431** of the deposition nozzle **430** to remove the deposition material M accumulated inside the spray passage **431** of the deposition nozzle **430**. The deposition nozzle cleaning step may include a first driving step, a second driving step, a third driving step, a fourth driving step, a fifth driving step, and a sixth driving step.

[0095] Referring to FIG. 10, the first driving step may be a step in which the first heating member **730** is moved to the right side (right side in FIG. 10) in the second direction DR2 by the first driver **740** and positioned above the deposition nozzle **430**. In the first driving step, as the actuator of the

first driver **740** is driven, the first stage may be moved from the first moving block **720** to the right side (right side in FIG. 5) in the second direction DR2, and as the second stage is pulled out from the first stage to the right side in the second direction DR2, the first heating member **730** may be positioned above the deposition nozzle **430**.

[0096] Referring to FIG. 11, the second driving step may be a step in which the first heating member **730** positioned above the deposition nozzle **430** is rotated to face the deposition nozzle **430** by the second driver **750**. In the second driving step, the second driver **750** may be rotated around the rotation shaft, so that the extended end of the first heating member **730** may be rotated to face the lower side (lower side in FIG. 11) in the third direction DR3. In other words, in the second driving step, the extended end of the first heating member **730** may be rotated to face the deposition nozzle **430** by the second driver **750**.

[0097] Referring to FIG. 12, the third driving step may be a step in which the first heating member **730** rotated to face the deposition nozzle **430** is inserted into the deposition nozzle **430** by the third driver **760**. In the third driving step, as the actuator of the third driver **760** is driven, the third driver **760** may be moved from the second driver **750** to the lower side (lower side in FIG. 12) in the third direction DR3, and as the third driver **760** is moved to the lower side in the third direction DR3, the first heating member **730** may be inserted into the spray passage **431** of the deposition nozzle **430**. The first heating member **730** inserted into the spray passage **431** of the deposition nozzle **430** may heat the deposition material accumulated in the spray passage **431** of the deposition nozzle **430** and vaporize and remove the deposition material.

[0098] Referring to FIG. 13, the fourth driving step may be a step in which the first heating member **730** inserted into the spray passage **431** of the deposition nozzle **430** is pulled out from the spray passage **431** of the deposition nozzle **430** by the third driver **760**. In the fourth driving step, as the actuator of the third driver **760** is driven, the third driver **760** may be moved to the upper side (upper side in FIG. 13) in the third direction DR3, and as the third driver **760** is moved to the upper side in the third direction DR3, the first heating member **730** may be pulled out from the spray passage **431** of the deposition nozzle **430**.

[0099] Referring to FIG. 14, the fifth driving step may be a step in which the first moving block **720** is moved along the first moving rail **710** so that the first heating member **730** pulled out from the spray passage **431** of the deposition nozzle **430** is positioned above another adjacent deposition nozzle **430**. In the fifth driving step, as the moving driver is driven so that the first heating member **730** is positioned above another deposition nozzle **430** adjacent to the deposition nozzle **430** into which the first heating member **730** was inserted, the first moving block **720** may be moved in the left side (left side in FIG. 14) in the first direction DR1 along the first moving rail **710**.

[0100] Referring to FIG. 15, the sixth driving step may be a step in which the first heating member **730** positioned above another deposition nozzle **430** is inserted into the another deposition nozzle **430** by the third driver **760**. In the sixth driving step, as the actuator of the third driver **760** is driven, the third driver **760** may be moved to the lower side (lower side in FIG. 15) in the third direction DR3, and as the third driver **760** is moved to the lower side in the third direction DR3, the first heating member **730** may be inserted into the spray passage **431** of the another deposition nozzle **430**. The first heating member **730** inserted into the spray passage **431** of the another deposition nozzle **430** may heat the deposition material accumulated in the spray passage **431** of the another deposition nozzle **430** and vaporize and remove the deposition material. In case that the deposition material accumulated inside another deposition nozzle **430** is removed, the fifth driving step and the sixth driving step may be repeatedly performed to remove all the deposition materials accumulated in the deposition nozzles **430**.

[0101] The above description is an example of technical features of the disclosure, and those skilled in the art to which the disclosure pertains will be able to make various modifications and variations. Therefore, the embodiments of the disclosure described above may be implemented separately or in combination with each other.

[0102] Therefore, the embodiments disclosed in the disclosure are not intended to limit the technical spirit of the disclosure, but to describe the technical spirit of the disclosure, and the scope of the technical spirit of the disclosure is not limited by these embodiments. The protection scope of the disclosure should be interpreted by the following claims, and it should be interpreted that all technical spirits within the equivalent scope are included in the scope of the disclosure.

Claims

1. A depositing apparatus comprising: a deposition source including at least one deposition nozzle that sprays a deposition material; a spray angle limiting portion spaced apart from the deposition source and limiting a spray angle of the deposition material sprayed from the at least one deposition nozzle; and a cleaning module disposed between the deposition source and the spray angle limiting portion and heating the deposition material accumulated on the spraying angle limiting portion.
2. The depositing apparatus of claim 1, wherein the cleaning module is disposed closer to the spray angle limiting portion than the deposition source.
3. The depositing apparatus of claim 1, wherein the at least one deposition nozzle includes a plurality of deposition nozzles, the plurality of deposition nozzles are arranged in a first direction, and the cleaning module is disposed to be movable in the first direction.
4. The depositing apparatus of claim 3, wherein the spray angle limiting portion includes: an extension plate extending to an upper direction from the deposition source; and a blocking plate extending from the extension plate in a second direction and forming an open area through which the deposition material passes.
5. The depositing apparatus of claim 4, wherein the second direction is a direction horizontally orthogonal to the first direction.
6. The depositing apparatus of claim 5, wherein the open area is disposed above the plurality of deposition nozzles and extends in the first direction.
7. The depositing apparatus of claim 6, wherein the cleaning module includes: a moving rail extending in the first direction below the blocking plate; a moving block disposed on the moving rail and moving along the moving rail; and a heating member extending from the moving block in the second direction.
8. The depositing apparatus of claim 7, wherein the cleaning module further includes a first driver connecting the moving block and the heating member and moving the heating member in the second direction.
9. The depositing apparatus of claim 8, wherein the cleaning module further includes a second driver connecting the first driver and the heating member and rotating the heating member so that an extended end of the heating member faces a third direction.
10. The depositing apparatus of claim 9, wherein the third direction is a direction vertically orthogonal to the first direction and the second direction.
11. The depositing apparatus of claim 10, wherein the cleaning module further includes a third driver connecting the second driver and the heating member and moving the heating member in the third direction.
12. The depositing apparatus of claim 11, wherein the heating member is moved by the third driver and inserted into one of the plurality of deposition nozzles.
13. The depositing apparatus of claim 4, wherein the extension plate includes a plurality of extension plates, the plurality of extension plates include a first extension plate and a second extension plate, the first extension plate extends in an upper direction from a side of the deposition source, and the second extension plate extends in an upper direction from another side of the deposition source so that the plurality of deposition nozzles are disposed between the first extension plate and the second extension plate.
14. The depositing apparatus of claim 13, wherein the blocking plate includes a plurality of

blocking plates, the plurality of blocking plates include a first blocking plate and a second blocking plate, the first blocking plate extends from the first extension plate in the second direction so as to be directed to an upper side of the plurality of deposition nozzles, the second blocking plate extends from the second extension plate in the second direction to face the first blocking plate, and an extended end of the first blocking plate and an extended end of the second blocking plate are spaced apart from each other, so that the open area is formed between the first blocking plate and the second blocking plate.

15. The depositing apparatus of claim 14, wherein the cleaning module includes a plurality of cleaning modules, the plurality of cleaning modules include a first cleaning module and a second cleaning module, the first cleaning module is disposed below the first blocking plate, and the second cleaning module is disposed below the second blocking plate.

16. A cleaning method of a depositing apparatus, the cleaning method comprising: cleaning a spray angle limiting portion including moving a cleaning module disposed below the spray angle limiting portion that limits a spray angle of a deposition material sprayed from a deposition nozzle along the spray angle limiting portion, and removing the deposition material accumulated on the spray angle limiting portion by a heating member of the cleaning module; and cleaning the deposition nozzle including inserting the heating member into the deposition nozzle to remove the deposition material accumulated in the deposition nozzle.

17. The cleaning method of claim 16, wherein the deposition nozzle includes a plurality of deposition nozzles arranged in a first direction, the spray angle limiting portion includes a blocking plate that forms an open area through which the deposition material passes extending in the first direction above the plurality of deposition nozzles, and the cleaning of the spray angle limiting portion includes moving the cleaning module in the first direction below the blocking plate.

18. The cleaning method of claim 17, wherein the cleaning module further includes: a moving rail extending in the first direction below the blocking plate; and a moving block supporting the heating member and disposed on the moving rail to move along the moving rail, and the cleaning of the spray angle limiting portion includes moving the moving block along the moving rail.

19. The cleaning method of claim 18, wherein the cleaning module further includes: a first driver moving the heating member in a second direction horizontally orthogonal to the first direction and positioning the heating member above the plurality of deposition nozzles; a second driver rotating the heating member to a third direction vertically orthogonal to the first direction and the second direction so that the heating member faces the plurality of deposition nozzles; and a third driver moving the heating member in the third direction so that the heating member is inserted into one of the plurality of deposition nozzles, and the cleaning of the deposition nozzle further includes: moving the heating member in the second direction by the first driver and positioning the heating member above the plurality of deposition nozzles; rotating the heating member positioned above the one of the plurality of deposition nozzles by the second driver to face the one of the plurality of deposition nozzles; and inserting the heating member rotated to face the one of the plurality of deposition nozzles into the one of the plurality of deposition nozzles by the third driver.

20. The cleaning method of claim 19, wherein the cleaning of the deposition nozzle further includes: moving the heating member inserted into the one of the plurality of deposition nozzles in the third direction by the third driver so that the heating member is pulled out from the one of the plurality of deposition nozzles; moving the moving block along the moving rail so that the heating member pulled out from the one of the plurality of deposition nozzles is positioned above another one of the plurality of deposition nozzles adjacent to the one of the plurality of deposition nozzles; and inserting the heating member positioned above the another one of the plurality of deposition nozzles into the another one of the plurality of deposition nozzles by the third driver.
