

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12403711

Kind Code

B2

Date of Patent

September 02, 2025

Inventor(s)

Watanabe; Maho et al.

Laminate, card, and housing

Abstract

The laminate includes: a base material; an intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the intermediate layer. The accommodation part is provided in a part of a plane of the intermediate layer, and the accommodation part is a through hole penetrating in the thickness direction of the intermediate layer or a recess recessed in the thickness direction of the intermediate layer. The recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin. The base material, the intermediate layer, and the overlay layer contain the same type of resin material. The base material and the intermediate layer are bonded to each other by fusion, and the intermediate layer and the overlay layer are bonded to each other by fusion.

Inventors: Watanabe; Maho (Tokyo, JP), Amago; Hirohisa (Tokyo, JP), Kaino; Yuriko (Tokyo, JP), Takagi; Kenji (Tokyo, JP), Yamano; Ryota (Tokyo, JP), Mizuno; Hiroshi (Tokyo, JP), Tejima; Aya (Tokyo, JP)

Applicant: Sony Group Corporation (Tokyo, JP)

Family ID: 82159843

Assignee: Sony Group Corporation (Tokyo, JP)

Appl. No.: 18/268882

Filed (or PCT Filed): December 22, 2021

PCT No.: PCT/JP2021/047702

PCT Pub. No.: WO2022/138766

PCT Pub. Date: June 30, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20240042784 A1	Feb. 08, 2024

Foreign Application Priority Data

JP	2020-212981	Dec. 22, 2020
----	-------------	---------------

Publication Classification

Int. Cl.:	B41M5/42 (20060101); B41M5/323 (20060101); B41M5/41 (20060101); B41M5/44 (20060101); B41M5/46 (20060101); B42D25/41 (20140101); B41M5/327 (20060101); B41M5/333 (20060101); B41M5/34 (20060101); B42D25/23 (20140101)
U.S. Cl.:	
CPC	B41M5/42 (20130101); B41M5/323 (20130101); B41M5/41 (20130101); B41M5/46 (20130101); B42D25/41 (20141001); B41M5/3275 (20130101); B41M5/3335 (20130101); B41M5/34 (20130101); B41M5/44 (20130101); B41M2205/04 (20130101); B41M2205/38 (20130101); B41M2205/42 (20130101); B42D25/23 (20141001)

Field of Classification Search

CPC:	B41M (5/323); B41M (5/3275); B41M (5/3335); B41M (5/34); B41M (5/41); B41M (5/42); B41M (5/44); B41M (5/46); B41M (2205/04); B41M (2205/38); B41M (2205/42); B42D (25/23); B42D (25/41)
------	---

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5534372	12/1995	Koshizuka et al.	N/A	N/A
2021/0316563	12/2020	Shuto et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1663814	12/2004	CN	N/A
101468564	12/2008	CN	N/A
101529451	12/2008	CN	N/A
102481754	12/2011	CN	N/A
103065546	12/2012	CN	N/A
109689394	12/2018	CN	N/A
111051076	12/2019	CN	N/A
1491354	12/2003	EP	N/A
1669208	12/2005	EP	N/A
3674099	12/2019	EP	N/A
2003118233	12/2002	JP	N/A

OTHER PUBLICATIONS

Primary Examiner: Higgins; Gerard

Attorney, Agent or Firm: K&L Gates LLP

Background/Summary

TECHNICAL FIELD

(1) The present disclosure relates to a laminate, a card, and a housing.

BACKGROUND ART

(2) In recent years, studies have been made on cards such as a security card, a financial settlement card (for example, a credit card, a cash card, and the like), an identification (ID) card (for example, an employee ID card, a membership card, a student ID card, and the like), and a personal transaction card (for example, a prepaid card, a point card, and the like), the cards including a recording medium configured to be capable of changing the colored state thereof by an external stimulus in order to prevent forgery. For example, Patent Document 1 discloses a forgery preventing structure in which a security device and a transparent protective sheet are sequentially disposed on a color development layer having a laser color development part.

CITATION LIST

Patent Document

(3) Patent Document 1: Japanese Patent Application Laid-Open No. 2019-38141

SUMMARY OF THE INVENTION

Problems to be Solved by the Invention

(4) In recent years, while improvement in convenience due to the spread of the various cards described above is expected, the forgery of the card has been a major problem. Furthermore, distribution of forged products of medical supplies, automobile parts, toys, foods, cosmetics, and electronic devices, and the like has also been a problem. Distribution of these forged products not only lowers the brand and image of companies, but also may affect the health and safety of users. Therefore, it is strongly desired to improve the forgery preventing property of cards and products.

(5) An object of the present disclosure is to provide a laminate, a card, and a housing that can improve the forgery preventing property.

Solutions to Problems

(6) In order to solve the above-described problem, a laminate according to the present disclosure includes: a base material; an intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the intermediate layer, in which the accommodation part is provided in a part of a plane of the intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the intermediate layer or a recess recessed in a thickness direction of the intermediate layer, the recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin, the base material, the intermediate layer, and the overlay layer contain the same type of resin material, and the base material and the intermediate layer are bonded to each other by fusion, and the intermediate layer and the overlay layer are bonded to each other by fusion.

(7) A laminate according to the present disclosure includes: a base material; an intermediate layer provided on the base material and having an accommodation part; a recording medium provided in

the accommodation part; and an overlay layer provided on the intermediate layer, in which the accommodation part is provided in a part of a plane of the intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the intermediate layer or a recess recessed in a thickness direction of the intermediate layer, the recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin, the base material, the intermediate layer, and the overlay layer contain the same type of resin material, and the base material and the intermediate layer are bonded to each other by a thermal adhesive, and the intermediate layer and the overlay layer are bonded to each other by a thermal adhesive.

Description

BRIEF DESCRIPTION OF DRAWINGS

- (1) FIG. 1 is a perspective view of a laminate according to a first embodiment of the present disclosure.
- (2) FIG. 2 is a cross-sectional view taken along line II-II of FIG. 1.
- (3) FIG. 3 is a cross-sectional view of a recording medium.
- (4) FIG. 4 is a cross-sectional view of a laminate according to a second embodiment of the present disclosure.
- (5) FIG. 5 is a cross-sectional view of a laminate according to a modification example of the first embodiment of the present disclosure.
- (6) FIG. 6 is a cross-sectional view of a modification example of the recording medium.
- (7) FIG. 7A is a plan view of a front surface of a smartphone. FIG. 7B is a plan view of a back surface of the smartphone.
- (8) FIG. 8 is a perspective view of a notebook personal computer.
- (9) FIG. 9 is a perspective view of a decorative container.
- (10) FIG. 10 is a cross-sectional view of a recording medium.
- (11) FIG. 11 is a view of a test apparatus for a 90 degree peel test.
- (12) FIG. 12A is a view for explaining a preparation process of a 90 degree peel test. FIG. 12B is a view of a test apparatus for a 90 degree peel test.
- (13) FIG. 13 is a perspective view of a laminate according to a third embodiment of the present disclosure.
- (14) FIG. 14 is a cross-sectional view taken along line XIV-XIV of FIG. 13.
- (15) FIG. 15 is a cross-sectional view of a recording medium.
- (16) FIG. 16 is a cross-sectional view of a laminate according to a fourth embodiment of the present disclosure.
- (17) FIG. 17 is a cross-sectional view of a laminate according to a modification example of the third embodiment of the present disclosure.
- (18) FIG. 18 is a cross-sectional view of a recording medium.
- (19) FIG. 19 is a cross-sectional view of a recording medium.
- (20) FIG. 20 is a cross-sectional view of a recording medium.
- (21) FIG. 21 is a cross-sectional view of a recording medium.
- (22) FIG. 22 is a cross-sectional view of a recording medium.
- (23) FIG. 23 is a cross-sectional view of a recording medium.
- (24) FIG. 24 is a cross-sectional view of a recording medium.
- (25) FIG. 25 is a perspective view of a booklet.
- (26) FIG. 26 is a graph showing measurement results of peel strength of a sample.

MODE FOR CARRYING OUT THE INVENTION

- (27) Embodiments of the present disclosure will be described in the following order. Note that, in

all the drawings of the following embodiments, the same or corresponding portions are denoted by the same reference numerals. 1 First Embodiment (example of laminate) 1.1 Configuration of laminate 1.2 Method for producing laminate 1.3 Recording method of laminate 1.4 Action and effect 2 Second Embodiment (example of laminate) 2.1 Configuration of laminate 2.2 Method for producing laminate 2.3 Action and effect 3 Third Embodiment (example of laminate) 3.1 Configuration of laminate 3.2 Action and effect 4 Fourth Embodiment (example of laminate) 4.1 Configuration of laminate 4.2 Action and effect 5 Modification examples 6 Reference examples and examples

1 First Embodiment

1.1 Configuration of Laminate

(28) FIG. 1 is a perspective view of a laminate **10** according to a first embodiment of the present disclosure. FIG. 2 is a cross-sectional view taken along line II-II of FIG. 1. The laminate **10** includes a base material **11**, an adhesive layer **12**, an intermediate layer **13**, an adhesive layer **14**, an overlay layer **15**, and a recording medium **20**. The laminate **10** may be a card (hereinafter, referred to as “security card or the like”), such as a security card, a financial settlement card (for example, a credit card, a cash card, and the like), an ID card (for example, an employee ID card, a membership card, a student ID card, and the like), or a personal transaction card (for example, a prepaid card, a point card, and the like).

(29) (Base Material)

(30) The base material **11** is a support that supports the recording medium **20** and the intermediate layer **13**. The base material **11** may be a card. The base material **11** may have a color such as white. In the base material **11**, a pattern, a picture, a photograph, a character, a combination of two or more thereof, or the like (hereinafter, referred to as “pattern or the like”) may be printed on one main surface of the base material **11** on a side on which the intermediate layer **13**, the recording medium **20**, and the like are provided.

(31) The base material **11** contains, for example, plastic. The base material **11** may contain at least one selected from the group consisting of a colorant, an antistatic agent, a flame retardant, a surface modifier, and the like, as necessary.

(32) The plastic includes, for example, at least one selected from the group consisting of an ester-based resin, an amide-based resin, an olefin-based resin, a vinyl-based resin, an acrylic resin, an imide-based resin, a styrene-based resin, engineering plastic, and the like. In a case where the base material **11** contains two or more resins, the two or more resins may be mixed, copolymerized, or laminated.

(33) The ester-based resin includes, for example, at least one selected from the group consisting of polyethylene terephthalate (PET), polybutylene terephthalate (PBT), polyethylene naphthalate (PEN), a polyethylene terephthalate-isophthalate copolymer, a terephthalic acid-cyclohexanedimethanol-ethylene glycol copolymer, and the like. The amide-based resin includes, for example, at least one selected from the group consisting of nylon 6, nylon 66, nylon 610, and the like. The olefin-based resin includes, for example, at least one selected from the group consisting of polyethylene (PE), polypropylene (PP), polymethylpentene (PMP), and the like. The vinyl-based resin includes, for example, polyvinyl chloride (PVC).

(34) The acrylic resin includes, for example, at least one selected from the group consisting of polyacrylate, polymethacrylate, polymethyl methacrylate (PMMA), and the like. The imide-based resin includes, for example, at least one selected from the group consisting of polyimide (PI), polyamideimide (PAI), polyetherimide (PEI), and the like. The styrene-based resin includes, for example, at least one selected from the group consisting of polycarbonate (PC), polystyrene (PS), high-impact polystyrene, an acrylonitrile-styrene resin (AS resin), an acrylonitrile-butadiene-styrene resin (ABS resin), and the like. The engineering plastic includes, for example, at least one selected from the group consisting of polycarbonate (PC), polyarylate (PAR), polysulfone (PSF), polyethersulfone (PES), polyphenylene ether (PPE), polyphenylene sulfide (PPS), polyether ketone

(PEK), polyether-ether ketone (PEEK), polyphenylene oxide (PPO), polyether sulfite, and the like.

(35) (Intermediate Layer)

(36) The intermediate layer **13** is provided on one main surface of the base material **11**, and the adhesive layer **12** is sandwiched between the base material **11** and the intermediate layer **13**. The intermediate layer **13** includes an accommodation part **13A** for accommodating the recording medium **20**. The accommodation part **13A** is provided in a part of the plane of the intermediate layer **13**. The accommodation part **13A** may be a through hole penetrating in the thickness direction of the intermediate layer **13**. The intermediate layer **13** is a layer for suppressing steps formed by the recording medium **20** when the recording medium **20** is sandwiched between the base material **11** and the overlay layer **15**. The intermediate layer **13** has substantially the same thickness as the recording medium **20**, and covers an area other than the area provided with the recording medium **20** in one main surface of the base material **11**.

(37) The intermediate layer **13** has a film shape. The intermediate layer **13** may have transparency. The intermediate layer **13** contains plastic. As the plastic, materials similar to those of the base material **11** can be exemplified.

(38) (Overlay Layer)

(39) The overlay layer **15** is provided above the intermediate layer **13** and the recording medium **20**, and covers the intermediate layer **13** and the recording medium **20**. The adhesive layer **14** is sandwiched between the intermediate layer **13** and the recording medium **20**, and the overlay layer **15**. The overlay layer **15** protects the members (that is, the recording medium **20** and the intermediate layer **13**) inside the laminate **10** and maintains the mechanical reliability of the laminate **10**.

(40) The overlay layer **15** has a film shape. The overlay layer **15** has transparency. The overlay layer **15** contains plastic. As the plastic, materials similar to those of the base material **11** can be exemplified. A pattern or the like may be printed on at least one main surface of the overlay layer **15**.

(41) (Adhesive Layer)

(42) The adhesive layer **12** is provided between the base material **11** and the intermediate layer **13** accommodating the recording medium **20**, and bonds the base material **11** and the intermediate layer **13** accommodating the recording medium **20** to each other. The adhesive layer **14** is provided between the intermediate layer **13** accommodating the recording medium **20** and the overlay layer **15**, and bonds the intermediate layer **13** accommodating the recording medium **20** and the overlay layer **15** to each other. The adhesive layers **12** and **14** have transparency. The adhesive layers **12** and **14** contain a thermal adhesive. The thermal adhesive contains a thermosetting resin. The thermosetting resin includes, for example, at least one selected from the group consisting of an epoxy-based resin, a urethane-based resin, and the like. The curing temperature of the thermal adhesive is preferably in a temperature range of 100° C. or higher and 120° C. or lower from the viewpoint of reducing damage to the recording medium **20**.

(43) (Recording Medium)

(44) FIG. 3 is a cross-sectional view of the recording medium **20**. The recording medium **20** is configured to be capable of changing the colored state thereof by an external stimulus. By this change in the colored state, for example, a pattern or the like can be recorded on the recording medium **20**. The external stimulus is laser light. The change in the colored state is preferably an irreversible change from the viewpoint of improving the forgery preventing property. That is, the system of the recording medium **20** is preferably a write once system in which a pattern or the like can be written only once. It is preferable that the recording medium **20** be fitted in the accommodation part **13A** of the intermediate layer **13**, and the recording medium **20** and the intermediate layer **13** be integrated. As a result, it is possible to make it difficult to visually recognize the boundary between the recording medium **20** and the intermediate layer **13** in the in-plane direction of the laminate **10**. Therefore, the forgery preventing property can be improved.

(45) The recording medium **20** includes a base material **21**, an intermediate layer **32A**, a color development layer **24**, an intermediate layer **32B**, a color development layer **27**, an intermediate layer **32C**, and a color development layer **30** in this order. More specifically, the recording medium **20** includes the base material **21**, a pressure-sensitive adhesive layer **22**, a heat insulating layer **23**, the color development layer **24**, a pressure-sensitive adhesive layer **25**, a heat insulating layer **26**, the color development layer **27**, a pressure-sensitive adhesive layer **28**, a heat insulating layer **29**, and the color development layer **30** in this order. As illustrated in FIG. 3, the recording medium **20** may further include a protective layer **31** on the color development layer **30**. As illustrated in FIG. 10, the recording medium **20** may further include an intermediate layer **32D** between the color development layer **30** and the protective layer **31**. The heat insulating layers **23**, **26**, and **29** are provided as necessary, and thus are not necessarily provided.

(46) (Base Material)

(47) The base material **21** is a support for supporting the color development layers **24**, **27**, **30**, and the like. The base material **21** preferably contains a material having excellent heat resistance and excellent dimensional stability in the planar direction. The base material **21** may have either a light transmitting property or a non-light transmitting property. The base material **21** may be, for example, a rigid substrate such as a wafer, or may be a flexible thin glass, film, paper, or the like. By using a flexible substrate as the base material **21**, a flexible (bendable) recording medium can be realized.

(48) Examples of the constituent material of the base material **21** include inorganic materials, metal materials, plastics, and the like. The inorganic material includes, for example, at least one selected from the group consisting of silicon (Si), silicon oxide (SiO.sub.X), silicon nitride (SiN.sub.X), aluminum oxide (AlO.sub.X), and the like. Silicon oxide includes glass, spin-on-glass (SOG), and the like. The metal material includes, for example, at least one selected from the group consisting of aluminum (Al), nickel (Ni), stainless steel, and the like. As the plastic, materials similar to those of the base material **11** can be exemplified.

(49) Note that a reflective layer (not illustrated) may be provided on at least one main surface of the base material **21**, or the base material **21** itself may have a function as a reflective layer. The base material **21** having such a configuration enables clearer color display.

(50) (Intermediate Layer)

(51) The intermediate layer **32A** is provided between the base material **21** and the color development layer **24**. The intermediate layer **32A** can bond the base material **21** and the color development layer **24**. The intermediate layer **32A** may be able to heat-insulate the base material **21** and the color development layer **24**, and suppress diffusion of the constituent material between the base material **21** and the color development layer **24**. The intermediate layer **32A** includes the pressure-sensitive adhesive layer **22** and the heat insulating layer **23**. The pressure-sensitive adhesive layer **22** is adjacent to the base material **21**, and the heat insulating layer **23** is adjacent to the color development layer **24**. However, the intermediate layer **32A** may include only the pressure-sensitive adhesive layer **22**.

(52) The intermediate layer **32B** is provided between the color development layer **24** and the color development layer **27**. The intermediate layer **32B** can bond the color development layer **24** and the color development layer **27**. The intermediate layer **32B** may be able to heat-insulate the color development layer **24** and the color development layer **27**, and suppress diffusion of the constituent material between the color development layer **24** and the color development layer **27**. The intermediate layer **32B** includes the pressure-sensitive adhesive layer **25** and the heat insulating layer **26**. However, the intermediate layer **32B** may include only the pressure-sensitive adhesive layer **25**.

(53) The intermediate layer **32C** is provided between the color development layer **27** and the color development layer **30**. The intermediate layer **32C** can bond the color development layer **27** and the color development layer **30**. The intermediate layer **32C** may be able to heat-insulate the color

development layer 27 and the color development layer 30, and suppress diffusion of the constituent material between the color development layer 27 and the color development layer 30. The intermediate layer 32C includes the pressure-sensitive adhesive layer 28 and the heat insulating layer 29. However, the intermediate layer 32C may include only the pressure-sensitive adhesive layer 28.

(54) The intermediate layer 32D is provided between the color development layer 30 and the protective layer 31. The intermediate layer 32D can bond the color development layer 30 and the protective layer 31. The intermediate layer 32D may be able to heat-insulate the color development layer 30 and the protective layer 31, and suppress diffusion of the constituent material between the color development layer 30 and the protective layer 31. The intermediate layer 32D includes a pressure-sensitive adhesive layer 33 and a heat insulating layer 34. However, the intermediate layer 32D may include only the pressure-sensitive adhesive layer 33.

(55) (Color Development Layer)

(56) The color development layers 24, 27, and 30 are configured to be capable of changing the colored state thereof by an external stimulus such as laser light or heat. The color development layers 24, 27, and 30 are formed using a material that enables stable recording and controlling of the color development state. The color development layers 24, 27, and 30 contain a coloring compound having an electron donating property, a developer having an electron accepting property and corresponding to the coloring compound, a matrix polymer (binder), and a photothermal conversion material. The color development layers 24, 27, and 30 may contain, as necessary, for example, at least one additive selected from the group consisting of a sensitizer, an ultraviolet absorbing material, and the like in addition to the above-described materials.

(57) The color development layers 24, 27, and 30 contain coloring compounds developing colors of different hues from one another. That is, the coloring compounds contained in the color development layers 24, 27, and 30 exhibit different colors in the color development state. The coloring compound contained in the color development layer 24 exhibits, for example, a cyan color in the color development state. The coloring compound contained in the color development layer 27 exhibits, for example, a magenta color in the color development state. The coloring compound contained in the color development layer 30 exhibits, for example, a yellow color in the color development state. The photothermal conversion materials contained in the color development layers 24, 27, and 30 absorb laser light in different wavelength ranges (for example, near-infrared laser light different from each other) and generate heat.

(58) The thickness of each of the color development layers 24, 27, and 30 is preferably 1 μm or more and 20 μm or less, and more preferably 2 μm or more and 15 μm or less. When the thickness of each of the color development layers 24, 27, and 30 is 1 μm or more, a sufficient color development density can be obtained. On the other hand, when the thickness of each of the color development layers 24, 27, and 30 is 20 μm or less, it is possible to suppress the heat utilization amount of each of the color development layers 24, 27, and 30 from becoming too large. Therefore, deterioration of color developability can be suppressed.

(59) (Coloring Compound)

(60) The coloring compound is, for example, leuco dye. The leuco dye may be, for example, an existing dye for heat-sensitive paper. Specific examples thereof include a compound including a group having an electron donating property in the molecule, represented by the following Formula (1).

(61) ##STR00001##

(62) The coloring compound is not particularly limited, and can be selected as appropriate according to the purpose. Specific examples of the coloring compound include, in addition to the compound represented by Formula (1) described above, a fluoran-based compound, a triphenylmethane phthalide-based compound, an azaphthalide-based compound, a phenothiazine-based compound, a leucoauramine-based compound, an indolinophthalide-based compound, and

the like. Other examples thereof include 2-anilino-3-methyl-6-diethylaminofluoran, 2-anilino-3-methyl-6-di(n-butylamino)fluoran, 2-anilino-3-methyl-6-(N-n-propyl-N-methylamino)fluoran, 2-anilino-3-methyl-6-(N-isopropyl-N-methylamino)fluoran, 2-anilino-3-methyl-6-(N-isobutyl-N-methylamino)fluoran, 2-anilino-3-methyl-6-(N-n-amyl-N-methylamino)fluoran, 2-anilino-3-methyl-6-(N-sec-butyl-N-methylamino)fluoran, 2-anilino-3-methyl-6-(N-n-amyl-N-ethylamino)fluoran, 2-anilino-3-methyl-6-(N-iso-amyl-N-ethylamino)fluoran, 2-anilino-3-methyl-6-(N-n-propyl-N-isopropylamino)fluoran, 2-anilino-3-methyl-6-(N-cyclohexyl-N-methylamino)fluoran, 2-anilino-3-methyl-6-(N-ethyl-p-toluidino)fluoran, 2-anilino-3-methyl-6-(N-methyl-p-toluidino)fluoran, 2-(m-trichloromethylanilino)-3-methyl-6-diethylaminofluoran, 2-(m-trifluoromethylanilino)-3-methyl-6-diethylaminofluoran, 2-(m-trichloromethylanilino)-3-methyl-6-(N-cyclohexyl-N-methylamino)fluoran, 2-(2,4-dimethylanilino)-3-methyl-6-diethylaminofluoran, 2-(N-ethyl-p-toluidino)-3-methyl-6-(N-ethylanilino)fluoran, 2-(N-ethyl-p-toluidino)-3-methyl-6-(N-propyl-p-toluidino)fluoran, 2-anilino-6-(N-n-hexyl-N-ethylamino)fluoran, 2-(o-chloroanilino)-6-diethylaminofluoran, 2-(o-chloroanilino)-6-dibutylaminofluoran, 2-(m-trifluoromethylanilino)-6-diethylaminofluoran, 2,3-dimethyl-6-dimethylaminofluoran, 3-methyl-6-(N-ethyl-p-toluidino)fluoran, 2-chloro-6-diethylaminofluoran, 2-bromo-6-diethylaminofluoran, 2-chloro-6-dipropylaminofluoran, 3-chloro-6-cyclohexylaminofluoran, 3-bromo-6-cyclohexylaminofluoran, 2-chloro-6-(N-ethyl-N-isoamylamino)fluoran, 2-chloro-3-methyl-6-diethylaminofluoran, 2-anilino-3-chloro-6-diethylaminofluoran, 2-(o-chloroanilino)-3-chloro-6-cyclohexylaminofluoran, 2-(m-trifluoromethylanilino)-3-chloro-6-diethylaminofluoran, 2-(2,3-dichloroanilino)-3-chloro-6-diethylaminofluoran, 1,2-benzo-6-diethylaminofluoran, 3-diethylamino-6-(m-trifluoromethylanilino)fluoran, 3-(1-ethyl-2-methylindol-3-yl)-3-(2-ethoxy-4-diethylaminophenyl)-4-azaphthalide, 3-(1-ethyl-2-methylindol-3-yl)-3-(2-ethoxy-4-diethylaminophenyl)-7-azaphthalide, 3-(1-octyl-2-methylindol-3-yl)-3-(2-ethoxy-4-diethylaminophenyl)-4-azaphthalide, 3-(1-ethyl-2-methylindol-3-yl)-3-(2-methyl-4-diethylaminophenyl)-4-azaphthalide, 3-(1-ethyl-2-methylindol-3-yl)-3-(2-methyl-4-diethylaminophenyl)-7-azaphthalide, 3-(1-ethyl-2-methylindol-3-yl)-3-(4-diethylaminophenyl)-4-azaphthalide, 3-(1-ethyl-2-methylindol-3-yl)-3-(4-N-n-amyl-N-methylaminophenyl)-4-azaphthalide, 3-(1-methyl-2-methylindol-3-yl)-3-(2-hexyloxy-4-diethylaminophenyl)-4-azaphthalide, 3,3-bis(2-ethoxy-4-diethylaminophenyl)-4-azaphthalide, 3,3-bis(2-ethoxy-4-diethylaminophenyl)-7-azaphthalide, 2-(p-acetylanilino)-6-(N-n-amyl-N-n-butylamino)fluoran, 2-benzylamino-6-(N-ethyl-p-toluidino)fluoran, 2-benzylamino-6-(N-methyl-2,4-dimethylanilino)fluoran, 2-benzylamino-6-(N-ethyl-2,4-dimethylanilino)fluoran, 2-benzylamino-6-(N-methyl-p-toluidino)fluoran, 2-benzylamino-6-(N-ethyl-p-toluidino)fluoran, 2-(di-p-methylbenzylamino)-6-(N-ethyl-p-toluidino)fluoran, 2-(α -phenylethylamino)-6-(N-ethyl-p-toluidino)fluoran, 2-methylamino-6-(N-methylanilino)fluoran, 2-methylamino-6-(N-ethylanilino)fluoran, 2-methylamino-6-(N-propylanilino)fluoran, 2-ethylamino-6-(N-methyl-p-toluidino)fluoran, 2-methylamino-6-(N-methyl-2,4-dimethylanilino)fluoran, 2-ethylamino-6-(N-ethyl-2,4-dimethylanilino)fluoran, 2-dimethylamino-6-(N-methylanilino)fluoran, 2-dimethylamino-6-(N-ethyl-p-toluidino)fluoran, 2-dipropylamino-6-(N-methylanilino)fluoran, 2-dipropylamino-6-(N-ethylanilino)fluoran, 2-amino-6-(N-methylanilino)fluoran, 2-amino-6-(N-ethylanilino)fluoran, 2-amino-6-(N-propylanilino)fluoran, 2-amino-6-(N-methyl-p-toluidino)fluoran, 2-amino-6-(N-ethyl-p-toluidino)fluoran, 2-amino-6-(N-propyl-p-toluidino)fluoran, 2-amino-6-(N-methyl-p-ethylanilino)fluoran, 2-amino-6-(N-ethyl-p-ethylanilino)fluoran, 2-amino-6-(N-propyl-p-ethylanilino)fluoran, 2-amino-6-(N-methyl-2,4-dimethylanilino)fluoran, 2-amino-6-(N-ethyl-2,4-dimethylanilino)fluoran, 2-amino-6-(N-propyl-2,4-dimethylanilino)fluoran, 2-amino-6-(N-methyl-p-chloroanilino)fluoran, 2-amino-6-(N-ethyl-p-chloroanilino)fluoran, 2-amino-6-(N-propyl-p-chloroanilino)fluoran, 1,2-benzo-6-(N-ethyl-N-isoamylamino)fluoran, 1,2-benzo-6-

dibutylaminofluoran, 1,2-benzo-6-(N-methyl-N-cyclohexylamino)fluoran, 1,2-benzo-6-(N-ethyl-N-toluidino)fluoran, and the like. Each of the color development layers **24**, **27**, and **30** may contain one of the above-described coloring compounds alone or two or more thereof.

(63) (Developer)

(64) The developer is, for example, for causing a colorless coloring compound to develop color. The developer may have a particulate shape. Examples of the developer include at least one selected from the group consisting of a phenol derivative, a salicylic acid derivative, a urea derivative, and the like. Specific examples thereof include a hydroxybenzoic acid type compound including an electron-accepting group in the molecule, represented by the following Formula (2). The hydroxybenzoic acid type compound may be a bis(hydroxybenzoic acid) type compound.

(65) ##STR00002## (where X is any one of —NHCO—, —CONH—, —NHCONH—, —CONHCO—, —NHNHCO—, —CONHNH—, —CONHNHCO—, —NHCOCONH—, —NHCONHCO—, —CONHCONH—, —NHNHCONH—, —NHCONHNH—, —CONHNHCONH—, —NHCONHNHCO—, and —CONHNHCONH—, and R is a linear hydrocarbon group having from 25 to 34 carbon atoms.)

(66) The bonding positions of the hydroxy group (—OH), the carboxyl group (—COOH) and the —X—R group in Formula (2) are not limited. For example, the hydroxybenzoic acid type compound may have a structure in which a hydroxy group and a carboxyl group are bonded at the ortho position of benzene, that is, a salicylic acid skeleton.

(67) (Matrix Polymer)

(68) The matrix polymer (matrix resin) preferably has a function as a binder. The matrix polymer is preferably one with which the coloring compound, the developer, and the photothermal conversion material are easily homogeneously dispersed. Examples of the matrix polymer include at least one selected from the group consisting of a thermosetting resin and a thermoplastic resin. Specific examples thereof include at least one selected from the group consisting of a polyvinyl chloride-based resin, a polyvinyl acetate-based resin, a vinyl chloride-vinyl acetate copolymer resin, an ethyl cellulose-based resin, a polystyrene-based resin, a styrene-based copolymer resin, a phenoxy resin-based resin, a polyester-based resin, an aromatic polyester-based resin, a polyurethane-based resin, a polycarbonate-based resin, a polyacrylic acid ester-based resin, a polymethacrylic acid ester-based resin, an acrylic acid-based copolymer resin, a maleic acid-based polymer resin, a polyvinyl alcohol-based resin, a modified polyvinyl alcohol-based resin, a hydroxyethyl cellulose-based resin, a carboxymethyl cellulose-based resin, starch, and the like.

(69) The matrix polymer preferably contains a polycarbonate-based resin. When the matrix polymer contains a polycarbonate-based resin, the light resistance of the background of the recording medium **20** can be improved. Here, the polycarbonate-based resin is a resin having a carbonate group (—O—(C=O)—O—) as a structural unit at least in the main chain. Therefore, other structural units may be included in the main chain in addition to the carbonate group.

(70) The proportion of the developer in the total amount of the developer and the matrix resin is preferably 16 mass % or less. When the proportion of the developer is 16 mass % or less, the adhesion between the color development layers **24**, **27**, and **30** and layers adjacent to the color development layers **24**, **27**, and **30** (particularly, heat insulating layers **23**, **26**, **29**) can be improved.

(71) The proportion of the developer in the total amount of the developer and the matrix resin is measured as follows. The compositions of the developer and the matrix polymer of the color development layer are measured by performing mapping using a Fourier transform infrared spectrophotometer (micro FTIR). Alternatively, the proportion of the developer is calculated utilizing the difference in solubility between the developer and the matrix polymer as follows: each of the developer and the matrix polymer is dissolved in an appropriate organic solvent and the weight thereof is measured.

(72) From the viewpoint of improving the adhesion between the color development layers **24**, **27**, and **30** and layers adjacent to the color development layers **24**, **27**, and **30** (particularly, heat

insulating layers **23**, **26**, **29**), the content of the matrix polymer in the color development layers **24**, **27**, and **30** is preferably 84 mass % or more. From the viewpoint of suppressing a decrease in color developability of the color development layers **24**, **27**, and **30**, the content of the matrix polymer is preferably 50 mass % or more and 70 mass % or less, and more preferably 58 mass % or more and 65 mass % or less. In a case where the content of the matrix polymer is 50 mass % or more and 70 mass % or less, it is preferable to select a layer adjacent to the color development layers **24**, **27**, and **30** so as to obtain good adhesion.

(73) The content of the matrix polymer in the color development layers **24**, **27**, and **30** is measured as follows. The compositions of the developer and the matrix polymer of the color development layers **24**, **27**, and **30** are measured by performing mapping using a Fourier transform infrared spectrophotometer (micro FTIR). Alternatively, the content of the matrix polymer is calculated utilizing the difference in solubility among the contents of the color development layers **24**, **27**, and **30** as follows: each of the contents is dissolved in an appropriate organic solvent and the weight thereof is measured.

(74) (Photothermal Conversion Material)

(75) The photothermal conversion material absorbs light in a predetermined wavelength range of the near-infrared region and generates heat, for example. As the photothermal conversion material, for example, a near-infrared absorbing dye having an absorption peak in a wavelength range of 700 nm or more and 2,000 nm or less and having almost no absorption in the visible region is preferably used. Specific examples of the photothermal conversion material include at least one selected from the group consisting of a compound having a phthalocyanine skeleton (phthalocyanine-based dye), a compound having a squarylium skeleton (squarylium-based dye), an inorganic compound, and the like. Examples of the inorganic compound include at least one selected from the group consisting of a metal complex such as a dithio complex, a diimmonium salt, an aminium salt, an inorganic compound, and the like. Examples of the inorganic compound include at least one selected from the group consisting of graphite, carbon black, metal powder particles, metal oxides such as tricobalt tetraoxide, iron oxide, chromium oxide, copper oxide, titanium black, and indium tin oxide (ITO), metal nitrides such as niobium nitride, metal carbides such as tantalum carbide, metal sulfides, various magnetic powders, and the like. In addition, a compound having a cyanine skeleton (cyanine-based dye), the compound having excellent light resistance and heat resistance, may be used. Note that, here, the excellent light resistance means that the compound is not decomposed by, for example, irradiation with light of a fluorescent lamp or the like under a use environment. The excellent heat resistance means that, for example, when a film is formed using the compound together with a polymer material and the film is stored at 150° C. for 30 minutes, the maximum absorption peak value of the absorption spectrum does not change by 20% or more. Examples of such a compound having a cyanine skeleton include compounds having, in the molecule, at least one of a counter ion of any of SbF₆, PF₆, BF₄, ClO₄, CF₃SO₃, and (CF₃SO₃)₂N, or a methine chain including a 5-membered ring or a 6-membered ring. Note that the compound having a cyanine skeleton, used for the recording medium **20** in the first embodiment, preferably has both any one of the counter ions described above and a cyclic structure such as a 5-membered ring and a 6-membered ring in a methine chain, and when the compound has at least one of the counter ion or the cyclic structure, sufficient light resistance and heat resistance are secured.

(76) Note that, as the photothermal conversion material, it is preferable to select, for example, a photothermal conversion material having a narrow light absorption band in a wavelength range of 700 nm or more and 2,000 nm or less, and having a light absorption band not overlapping among the color development layers **24**, **27**, and **30**. As a result, a desired layer among the color development layers **24**, **27**, and **30** can be selectively caused to develop color.

(77) (Heat Insulating Layer)

(78) The heat insulating layer **23** is provided between the base material **21** and the color

development layer **24**, and heat-insulates the base material **21** and the color development layer **24**. The heat insulating layer **26** is provided between the color development layer **24** and the color development layer **27**, and heat-insulates the color development layer **24** and the color development layer **27**. The heat insulating layer **29** is provided between the color development layer **27** and the color development layer **30**, and heat-insulates the color development layer **27** and the color development layer **30**. The heat insulating layer **34** is provided between the color development layer **30** and the protective layer **31**, and heat-insulates the color development layer **30** and the protective layer **31**. The heat insulating layers **23**, **26**, **29**, and **34** contain, for example, a general polymer material having translucency. Specific examples of the material include at least one selected from the group consisting of an acrylic resin, a polyvinyl chloride-based resin, a polyvinyl acetate-based resin, a vinyl chloride-vinyl acetate copolymer resin, an ethyl cellulose-based resin, a polystyrene-based resin, a styrene-based copolymer resin, a phenoxy resin-based resin, a polyester-based resin, an aromatic polyester-based resin, a polyurethane-based resin, a polycarbonate-based resin, a polyacrylic acid ester-based resin, a polymethacrylic acid ester-based resin, an acrylic acid-based copolymer resin, a maleic acid-based polymer resin, a polyvinyl alcohol-based resin, a modified polyvinyl alcohol-based resin, a hydroxyethyl cellulose-based resin, a carboxymethyl cellulose-based resin, starch, and the like. Note that the heat insulating layers **23**, **26**, **29**, and **34** may contain, for example, various additives such as an ultraviolet absorber.

(79) The heat insulating layers **23**, **26**, **29**, and **34** may be ultraviolet curable resin layers. The ultraviolet curable resin layer contains an ultraviolet curable resin composition solidified by a polymerization reaction. More specifically, for example, the ultraviolet curable resin layer contains a polymer of a polymerizable compound and a polymerization initiator whose structure has been changed due to an active species generated by irradiation with external energy (ultraviolet rays). The ultraviolet curable resin composition includes, for example, at least one selected from the group consisting of a radically polymerizable ultraviolet curable resin composition, cationically polymerizable ultraviolet curable resin composition, and the like. The ultraviolet curable resin composition may contain, as necessary, at least one selected from the group consisting of a sensitizer, a filler, a stabilizer, a leveling agent, an antifoaming agent, a viscosity modifier, and the like. The ultraviolet curable resin composition may be an ultraviolet curable resin composition for a hard coat. The ultraviolet curable resin composition may be an acrylic ultraviolet curable resin composition.

(80) The heat insulating layers **23**, **26**, **29**, and **34** may contain an inorganic material having translucency. For example, when porous silica, alumina, titania, carbon, a composite thereof, or the like is used, the thermal conductivity is lowered, and the heat insulating effect is high, which is preferable. The heat insulating layers **23**, **26**, and **29** can be formed by, for example, a sol-gel method.

(81) The formation of physical steps may be suppressed by adjusting the thickness of the heat insulating layers **23**, **26**, **29**, and **34** to thereby make the thickness of the recording medium **20** equal to the thickness of the intermediate layer **13**. The thickness of the heat insulating layers **23**, **26**, **29**, and **34** is preferably 3 μm or more and 100 μm or less, and more preferably 5 μm or more and 50 μm or less. When the thickness of the heat insulating layers **23**, **26**, **29**, and **34** is 3 μm or more, a sufficient heat insulating effect can be obtained. On the other hand, when the thickness of the heat insulating layers **23**, **26**, **29**, and **34** is 100 μm or less, deterioration of translucency can be suppressed. In addition, a decrease in bending resistance of the recording medium **20** can be suppressed, and defects such as cracks can be made less likely to occur.

(82) The pencil hardness of the surfaces of the heat insulating layers **23**, **26**, **29**, and **34** is preferably 2B or more, and more preferably H or more. When the pencil hardness of the surfaces of the heat insulating layers **23**, **26**, **29**, and **34** is 2B or more, the density of the heat insulating layers **23**, **26**, **29**, and **34** is high, so that diffusion of substances via the intermediate layers **32A**, **32B**, **32C**, and **32D** can be further suppressed. For example, in a case where the pencil hardness of the

surfaces of the heat insulating layers **26** and **29** is 2B or more, diffusion of the coloring compound via the intermediate layers **32B** and **32C** can be further suppressed. Therefore, the hue change of the color development layers **24**, **27**, and **30** during long-term storage and the like can be further suppressed. As the heat insulating layers **23**, **26**, **29**, and **34** having the above-described pencil hardness, an ultraviolet curable resin layer is preferable.

(83) The pencil hardness of the surface of the heat insulating layer **23** is measured as follows. First, the laminate **10** is disassembled to expose the surface of the heat insulating layer **23**. Next, the pencil hardness of the surface of the heat insulating layer **23** is measured in accordance with JIS K5600-5-4. The measurement is performed in an atmosphere in a standard state at a temperature of $23\pm 1^{\circ}\text{C}$. and a relative humidity of $50\pm 5\%$. The pencil hardness of the surfaces of the heat insulating layers **26**, **29**, and **34** is also measured in a similar procedure to the pencil hardness of the surface of the heat insulating layer **23**.

(84) (Pressure-Sensitive Adhesive Layer)

(85) The pressure-sensitive adhesive layer **22** is provided between the base material **21** and the heat insulating layer **23**, and bonds the base material **21** and the heat insulating layer **23** to each other. The pressure-sensitive adhesive layer **25** is provided between the color development layer **24** and the heat insulating layer **26**, and bonds the color development layer **24** and the heat insulating layer **26** to each other. The pressure-sensitive adhesive layer **28** is provided between the color development layer **27** and the heat insulating layer **29**, and bonds the color development layer **27** and the heat insulating layer **29** to each other. The pressure-sensitive adhesive layer **33** is provided between the color development layer **30** and the heat insulating layer **34**, and bonds the color development layer **30** and the heat insulating layer **34** to each other. In a case where the recording medium **20** does not include the heat insulating layer **23**, the pressure-sensitive adhesive layer **22** bonds the base material **21** and the color development layer **24**. In this case, the pressure-sensitive adhesive layer **22** may have a function as a heat insulating layer and/or a diffusion preventing layer. In a case where the recording medium **20** does not include the heat insulating layer **26**, the pressure-sensitive adhesive layer **25** bonds the color development layer **24** and the color development layer **27**. In this case, the pressure-sensitive adhesive layer **25** may have a function as a heat insulating layer and/or a diffusion preventing layer. In a case where the recording medium **20** does not include the heat insulating layer **29**, the pressure-sensitive adhesive layer **28** bonds the color development layer **27** and the color development layer **30**. In this case, the pressure-sensitive adhesive layer **28** may have a function as a heat insulating layer and/or a diffusion preventing layer. In a case where the recording medium **20** does not include the heat insulating layer **34**, the pressure-sensitive adhesive layer **33** bonds the color development layer **30** and the protective layer **31**. In this case, the pressure-sensitive adhesive layer **33** may have a function as a heat insulating layer and/or a diffusion preventing layer. In the present specification, the term “and/or” means at least one, and for example, in the case of “X and/or Y”, it means three ways of only X, only Y, X and Y.

(86) The pressure-sensitive adhesive layers **22**, **25**, **28**, and **33** contain a pressure-sensitive adhesive. The pressure-sensitive adhesive includes, for example, at least one selected from the group consisting of an acrylic resin, a silicone-based resin, a urethane-based resin, an epoxy-based resin, and an elastomer-based material.

(87) (Protective Layer)

(88) The protective layer **31** is a layer for protecting the surface of the recording medium **20**, and is formed using, for example, at least one of an ultraviolet curable resin or a thermosetting resin. The protective layer **31** is preferably a hard coat layer. The thickness of the protective layer **31** is, for example, $0.1\text{ }\mu\text{m}$ or more and $20\text{ }\mu\text{m}$ or less.

(89) (Average Peel Strength Between Layers)

(90) The average peel strength at the interface between the layers constituting the laminate **10** is preferably 3.5 N/cm or more, more preferably 4.0 N/cm or more, still more preferably 4.5 N/cm or

more, and particularly preferably 5.0 N/cm or more. When the average peel strength at the interface between the layers is 3.5 N/cm or more, peeling at the interface between the layers constituting the laminate **10** can be suppressed. Therefore, the forgery preventing property and the falsification preventing property of the laminate **10** can be improved. Here, the layers constituting the laminate **10** may include the layers constituting the recording medium **20**.

(91) The average peel strength at the interface between the layers is determined by performing a 90 degree peel test. Since the method for measuring the average peel strength at the interface between the layers is similar, only the method for measuring the average peel strength at the interface between the heat insulating layer **26** and the color development layer **27** will be described below with reference to FIG. **11**.

(92) First, the laminate **10** is cut into a band shape having a width of 10 mm and a length of 100 mm to prepare a test piece **60**, and the test piece **60** is left for 24 hours or more in an atmosphere in a standard state at a temperature of $23\pm 1^{\circ}\text{C}$. and a relative humidity of $50\pm 5\%$. Note that, in a case where the average peel strength at the interface included in the recording medium **20** is measured, the test piece **60** is cut out so as to include the recording medium **20**. Hereinafter, in the test piece **60**, a laminate on the lower side of the interface between the heat insulating layer **26** and the color development layer **27** is referred to as an adherend **60A**, and a laminate on the upper side of the interface is referred to as an adherend **60B** (see, FIG. **3**). Next, at one end in the longitudinal direction of the test piece **60**, a cut is made between the adherend **60A** and the adherend **60B** with a sharp blade such as a cutter, the adherend **60B** is peeled off by a length of 20 mm in the longitudinal direction to make a gripping margin, and then the surface of the test piece **60** on the adherend **60A** side is fixed to a test stand **71** with a strong pressure-sensitive adhesive. As the pressure-sensitive adhesive, a pressure-sensitive adhesive having sufficiently high pressure-sensitive adhesive force, for example, a strong pressure-sensitive adhesive tape, scotch (registered trademark) manufactured by 3M Company, is selected so that the test piece **60** is not peeled off from the test stand **71** in the measurement of the peeling strength between the heat insulating layer **26** and the color development layer **27**.

(93) Next, one end of a tension member **61** is bonded to the surface of the adherend **60B** on the color development layer **27** side. As the tension member **61**, a band-shaped film having a strength enough to prevent elongation or breakage in the measurement of the peeling strength is used. In addition, one end of the tension member **61** is bonded to the adherend **60B** with a sufficiently high adhesive force so that the tension member **61** is not peeled off from the adherend **60A** in the measurement of the peeling strength. FIG. **11** illustrates an example in which the tension member **61** is used as a gripping margin, but in a case where there is a sufficient stroke for which the adherend **60B** is sandwiched with a clamp apparatus (metal plate) **62**, the adherend **60B** may be directly clamped without using the tension member **61**.

(94) Next, the gripping margin of the tension member **61** is passed between a pair of movable rolls **73A** and **73B** of a jig **72**, and the gripping margin is then sandwiched and fixed by 10 mm or more with the clamp apparatus (metal plate) **62** of a tensile compression tester SV-55C 2H manufactured by IMADA-SS Corporation. The movable rolls **73A** and **73B** serve as fulcrums of peeling in the 90 degree peel test. Next, the 90 degree peel test is performed with a tensile compression tester, the test force [N/10 mm] and the stroke [mm] are monitored as voltage values in, for example, a data logger manufactured by Keyence Corporation, and the voltage values are converted into forces and stored in a memory as CSV output data. Note that the 90 degree peel test is performed at a tensile speed of 5 mm/sec in a standard state of a temperature of $23\pm 1^{\circ}\text{C}$. and a relative humidity of $50\pm 5\%$. The stroke is set to 50 mm or more.

(95) The 90 degree peel test is performed three times in total, a position where the peeling strength is stabilized (a position where the rising of the force becomes gentle) is set as a start point (0 mm), and CSV output data from the start point to a position at a distance of 50 mm relatively away from the start point is arithmetically averaged to calculate an average value. As a result, the average peel

strength between the heat insulating layer **26** and the color development layer **27** is determined. Provided that, in a case where there is a point (spike) at which the peel force suddenly decreases in the CSV output data, the average peel strength is calculated excluding the point (spike).

(96) The average value of the minimum peel strengths among the peel strengths between the layers constituting the laminate **10** is preferably 3.5 N/cm or more, more preferably 4.0 N/cm or more, still more preferably 4.5 N/cm or more, and particularly preferably 5.0 N/cm or more. When the average value of the minimum peel strength is 3.5 N/cm or more as described above, peeling between the layers constituting the laminate **10** can be suppressed. Therefore, the forgery preventing property and the falsification preventing property of the laminate **10** can be improved. Here, the layers constituting the laminate **10** may include the layers constituting the recording medium **20**.

(97) The average value of the minimum peel strengths among the peel strengths between the layers constituting the laminate **10** is determined by performing a 90 degree peel test. Hereinafter, a method for measuring the average value of the minimum peel strengths among the peel strengths between the layers will be described with reference to FIGS. **12A** and **12B**.

(98) First, the laminate **10** is cut into a band shape having a width of 10 mm and a length of 100 mm to prepare the test piece **60**, and the test piece **60** is left for 24 hours or more in an atmosphere in a standard state at a temperature of $23\pm 1^{\circ}\text{C}$. and a relative humidity of $50\pm 5\%$. Next, as illustrated in FIG. **12A**, the surface of the test piece **60** on the base material **11** side is fixed to the test stand **71** with a strong pressure-sensitive adhesive, and the tension member **61** is bonded to the surface of the test piece **60** on the overlay layer **15** side. As the tension member **61**, a band-shaped film having a strength enough to prevent elongation or breakage in the measurement of the average peel strength is used. In addition, one end of the tension member **61** is bonded to the adherend **60B** with a sufficiently high adhesive force so as not to be peeled off from the adherend **60B** in the measurement of the average peel strength.

(99) Next, as illustrated in FIG. **12B**, the gripping margin of the tension member **61** is passed between the pair of movable rolls **73A** and **73B** of the jig **72**, and the gripping margin is then sandwiched and fixed by 10 mm or more with the clamp apparatus (metal plate) **62** of a tensile compression tester SV-55C 2H manufactured by IMADA-SS Corporation. Subsequent processes are similar to the method for measuring the average peel strength at the interface between the heat insulating layer **26** and the color development layer **27**. As described above, the average value of the minimum peel strengths among the peel strengths between the layers constituting the laminate **10** is determined.

(100) An interface having the lowest average peel strength among the interfaces of the laminate **10** is preferably located between the color development layer **24** and the color development layer **27** or between the color development layer **27** and the color development layer **30**. When the laminate **10** is disassembled, the recording medium **20** is disassembled, so that it becomes difficult to take out and use the recording medium **20**. Therefore, the forgery preventing property of the laminate **10** can be improved.

(101) (Combination of Materials of Base Material, Intermediate Layer, and Overlay Layer)

(102) The base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain the same type of resin material from the viewpoint of improving adhesion. The resin material may be a thermoplastic resin. The base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain a polycarbonate (PC)-based resin or a polyethylene terephthalate (PET)-based resin from the viewpoint of environmental consideration. The base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain a polycarbonate (PC)-based resin or a polyvinyl chloride (PVC)-based resin from the viewpoint of improving durability. The base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain a polycarbonate (PC)-based resin from the viewpoint of improving adhesion, environmental consideration, and improving durability.

(103) It can be confirmed, for example, as follows that the base material **11**, the intermediate layer **13**, and the overlay layer **15** contain the same type of resin material. First, the base material **11**, the intermediate layer **13**, and the overlay layer **15** are taken out from the laminate **10**. Next, IR spectra of the base material **11**, the intermediate layer **13**, and the overlay layer **15** are acquired by infrared absorption spectrometry (IR). Next, by comparing the acquired IR spectra of the respective layers, it is confirmed that the base material **11**, the intermediate layer **13**, and the overlay layer **15** contain the same type of resin material.

(104) In addition, the type of the resin material contained in each of the base material **11**, the intermediate layer **13**, and the overlay layer **15** can be confirmed using the acquired IR spectrum of each layer.

1.2 Method for Producing Laminate

(105) Hereinafter, an example of a method for producing the laminate **10** according to the first embodiment of the present disclosure will be described.

(106) First, a thermosetting resin is applied as a thermal adhesive to one main surface of the base material **11** to form the adhesive layer **12**. Next, after the intermediate layer **13** is placed on the adhesive layer **12**, the recording medium **20** is fitted in the accommodation part **13A** of the intermediate layer **13**. Note that the intermediate layer **13**, in which the recording medium **20** is fitted in the accommodation part **13A** in advance, may be placed on the adhesive layer **12**. In addition, the adhesive layer **12** may be formed by applying a thermosetting resin onto the intermediate layer **13** in which the recording medium **20** is fitted in the accommodation part **13A** in advance, and then placing the intermediate layer **13** on the main surface of the base material **11** with the coating film interposed therebetween. Alternatively, the adhesive layer **12** may be formed by bonding a sheet formed in advance by, for example, applying a thermosetting resin to a separator to the main surface of the base material **11** or the intermediate layer **13** in which the recording medium **20** is fitted in the accommodation part **13A** in advance, by means of thermal lamination or the like.

(107) Next, a thermosetting resin as a thermal adhesive is applied onto the intermediate layer **13** to form the adhesive layer **14**, and then the overlay layer **15** is placed on the adhesive layer **14**. Next, the obtained laminate is sandwiched between metal plates and pressurized while being heated, thereby thermally curing the adhesive layer **12** and the adhesive layer **14**. The temperature applied to the laminate at the time of thermal curing is preferably 100° C. or higher and 120° C. or lower from the viewpoint of reducing damage to the recording medium **20**. As a result, the intended laminate **10** is obtained. The adhesive layer **14** may be formed by applying a thermosetting resin to the overlay layer **15** and then placing the overlay layer **15** on the intermediate layer **13** with the coating film interposed therebetween. Alternatively, the adhesive layer **14** may be formed by bonding a sheet formed in advance by, for example, applying a thermosetting resin to a separator to the overlay layer **15** or the intermediate layer **13** by means of thermal lamination or the like.

1.3 Recording Method of Laminate

(108) In the laminate **10** according to the first embodiment, for example, a pattern or the like can be recorded on the recording medium **20** as follows. Here, a case where the color development layers **24**, **27**, and **30** exhibit cyan, magenta, and yellow colors, respectively, will be described as an example.

(109) For example, the recording medium **20** is irradiated with infrared rays having a prescribed wavelength and a prescribed output via the overlay layer **15** by a semiconductor laser or the like. Here, in the case of causing the color development layer **24** to develop color, an infrared ray having a wavelength $\lambda_{\text{sub.1}}$ is applied to the color development layer **24** with energy to the extent that the color development layer **24** reaches the color development temperature. As a result, the photothermal conversion material contained in the color development layer **24** generates heat to cause a color reaction (color development reaction) between the coloring compound and the developer, and thus a cyan color is developed in the irradiated portion. Similarly, in the case of

causing the color development layer **27** to develop color, an infrared ray having a wavelength $\lambda_{\text{sub.2}}$ is applied to the color development layer **27** with energy to the extent that the color development layer **27** reaches the color development temperature. In the case of causing the color development layer **30** to develop color, an infrared ray having a wavelength $\lambda_{\text{sub.3}}$ is applied to the color development layer **30** with energy to the extent that the color development layer **30** reaches the color development temperature. As a result, the photothermal conversion materials contained in the color development layer **27** and the color development layer **30** each generate heat to cause a color reaction between the coloring compound and the developer, and thus a magenta color and a yellow color are developed in the irradiated portions, respectively. In this manner, it is possible to record a pattern or the like (for example, a full-color pattern or the like) by irradiating a randomly selected portion with infrared rays having a corresponding wavelength.

1.4 Action and Effect

(110) As described above, in the laminate **10** according to the first embodiment, the base material **11** and the intermediate layer **13** are bonded to each other by the adhesive layer **12** containing a thermal adhesive, and the intermediate layer **13** and the overlay layer **15** are bonded to each other by the adhesive layer **12** containing a thermal adhesive. As a result, the base material **11** and the intermediate layer **13**, and the intermediate layer **13** and the overlay layer **15** can be firmly bonded to each other. Therefore, the forgery preventing property of the laminate **10** can be improved. Furthermore, the falsification preventing property of the laminate **10** can be improved. Therefore, the security of the laminate **10** can be improved.

(111) Since the recording medium **20** includes the color development layers **24**, **27**, and **30**, a full-color photographic image or the like of the laminate **10** such as a plastic security card can be obtained.

(112) Since the laminate **10** includes the full-color recording medium **20** in a part of the plane of the laminate **10**, the cost can be reduced as compared with a case where the full-color recording medium **20** is provided on the entire surface of the laminate **10**.

(113) Since the recording medium **20** is fitted in the accommodation part **13A** of the intermediate layer **13**, it is possible to make it difficult to visually recognize the boundary between the recording medium **20** and the intermediate layer **13** in the in-plane direction of the laminate **10**. Therefore, it is difficult to identify a portion where the recording medium **20** is provided in the plane of the laminate **10**. Therefore, the forgery preventing property can be improved.

(114) Since the recording medium **20** is sealed in the laminate **10**, the influence of moisture on the recording medium **20** can be reduced.

(115) Since the recording medium **20** includes the heat insulating layers **23**, **26**, and **29**, the thickness of the recording medium **20** can be made equal to the thickness of the intermediate layer **13** by adjusting the thickness of the heat insulating layers **23**, **26**, and **29**. Therefore, it is possible to suppress the formation of physical steps at the boundary between the recording medium **20** and the intermediate layer **13**.

2 Second Embodiment

2.1 Configuration of Laminate

(116) FIG. **4** is a cross-sectional view of a laminate **40** according to a second embodiment of the present disclosure. The laminate **40** is different from the laminate **10** according to the first embodiment in that the laminate **40** does not include the adhesive layer **12** or the adhesive layer **14**, the base material **11** and the intermediate layer **13** are bonded to each other by fusion, and the intermediate layer **13** and the overlay layer **15** are bonded to each other by fusion.

(117) In the second embodiment, the base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain a thermoplastic resin as plastic. Since the base material **11**, the intermediate layer **13**, and the overlay layer **15** contain a thermoplastic resin, it is possible to enhance the interlayer adhesion strength by fusion. From the viewpoint of reducing damage to the recording medium **20**, the thermoplastic resin is preferably one that can thermally fuse the layers of

the laminate **40** in a temperature range of 130° C. or higher and 200° C. or lower.

(118) The base material **11**, the intermediate layer **13**, and the overlay layer **15** may contain the same type of thermoplastic resin, or the base material **11**, the intermediate layer **13**, and the overlay layer **15** do not necessarily contain the same type of thermoplastic resin. In a case where the base material **11**, the intermediate layer **13**, and the overlay layer **15** do not contain the same type of thermoplastic resin, one layer of the base material **11**, the intermediate layer **13**, and the overlay layer **15** may contain a different type of thermoplastic resin from resins of the other two layers, or the base material **11**, the intermediate layer **13**, and the overlay layer **15** may contain different types of thermoplastic resins.

(119) In a case where the base material **11**, the intermediate layer **13**, and the overlay layer **15** contain the same type of thermoplastic resin, the base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain at least one selected from the group consisting of a semi-crystalline thermoplastic resin and an amorphous thermoplastic resin from the viewpoint of improving the interlayer adhesion strength by fusion.

(120) The semi-crystalline thermoplastic resin includes, for example, at least one selected from the group consisting of polypropylene (PP), polyethylene (PE), polyacetal (POM), polyethylene terephthalate (PET), polybutylene terephthalate (PBT), polyphenylene sulfide (PPS), polyether ether ketone (PEEK), and the like.

(121) The amorphous thermoplastic resin includes, for example, at least one selected from the group consisting of ABS resin, polycarbonate (PC), a polymer alloy of ABS resin and PC (hereinafter, referred to as “ABS/PC polymer alloy”), AS resin, polystyrene (PS), polymethyl methacrylate (PMMA), polyphenylene oxide (PPO), polysulfone (PSU), polyvinyl chloride (PVC), polyetherimide (PEI), polyethersulfone (PES), and the like.

(122) In a case where the base material **11**, the intermediate layer **13**, and the overlay layer **15** do not contain the same type of thermoplastic resin, the base material **11**, the intermediate layer **13**, and the overlay layer **15** preferably contain an amorphous thermoplastic resin from the viewpoint of improving the interlayer adhesion strength by fusion.

(123) The combination of the amorphous thermoplastic resins contained in the two adjacent layers of the laminate **40** is preferably the following combinations. In a case where one of two adjacent layers of the laminate **40** contains ABS resin, the other layer preferably contains at least one selected from the group consisting of an ABS/PC polymer alloy, polycarbonate (PC), AS resin, polystyrene (PS), polymethyl methacrylate (PMMA), and polyvinyl chloride (PVC).

(124) In a case where one of two adjacent layers of the laminate **40** preferably contains an ABS/PC polymer alloy, the other layer preferably contains at least one selected from the group consisting of ABS resin, polycarbonate (PC), and polymethyl methacrylate (PMMA). In a case where one of two adjacent layers of the laminate **40** contains polycarbonate (PC), the other layer preferably contains at least one selected from the group consisting of an ABS resin, an ABS/PC polymer alloy, and polymethyl methacrylate (PMMA).

(125) In a case where one of two adjacent layers of the laminate **40** contains AS resin, the other layer preferably contains at least one selected from the group consisting of ABS resin, polystyrene (PS), polymethyl methacrylate (PMMA), and polyphenylene oxide (PPO). In a case where one of two adjacent layers of the laminate **40** contains polystyrene (PS), the other layer preferably contains at least one selected from the group consisting of AS resin and polyphenylene oxide (PPO).

(126) In a case where one of two adjacent layers of the laminate **40** contains polymethyl methacrylate (PMMA), the other layer preferably contains at least one selected from the group consisting of ABS resin, an ABS/PC polymer alloy, AS resin, and polyphenylene oxide (PPO). In a case where one of two adjacent layers of the laminate **40** contains polyphenylene oxide (PPO), the other layer preferably contains at least one selected from the group consisting of polycarbonate (PC), AS resin, polystyrene (PS), and polymethyl methacrylate (PMMA).

(127) In a case where one of two adjacent layers of the laminate **40** contains polysulfone (PSU), the other layer preferably contains polycarbonate (PC). In a case where one of two adjacent layers of the laminate **40** contains polyvinyl chloride (PVC), the other layer preferably contains ABS resin.

2.2 Method for Producing Laminate

(128) Hereinafter, an example of a method for producing the laminate **10** according to the second embodiment of the present disclosure will be described.

(129) First, the intermediate layer **13** is placed on one main surface of the base material **11**, and then the recording medium **20** is fitted in the accommodation part **13A** of the intermediate layer **13**. Note that the intermediate layer **13** in which the recording medium **20** is fitted in the accommodation part **13A** in advance may be placed on one main surface of the base material **11**. Next, the overlay layer **15** is placed on the intermediate layer **13**. Next, the obtained laminate is sandwiched between metal plates, and pressurized while being heated, thereby thermally fusing the base material **11** and the intermediate layer **13**, and thermally fusing the intermediate layer **13** and the overlay layer **15**. The temperature applied to the laminate at the time of thermal fusion is preferably 130° C. or higher and 200° C. or lower from the viewpoint of reducing damage to the recording medium **20** and from the viewpoint of exhibiting sufficient fusion strength. As a result, the intended laminate **40** is obtained.

2.3 Action and Effect

(130) As described above, in the laminate **40** according to the second embodiment, the base material **11** and the intermediate layer **13**, and the intermediate layer **13** and the overlay layer **15** are fused, respectively. As a result, the base material **11** and the intermediate layer **13**, and the intermediate layer **13** and the overlay layer **15** can be firmly bonded to each other. Therefore, the forgery preventing property of the laminate **40** can be improved. Furthermore, the falsification preventing property of the laminate **40** can be improved. Therefore, the security of the laminate **40** can be improved.

3 Third Embodiment

3.1 Configuration of Laminate

(131) FIG. **13** is a perspective view of a laminate **10A** according to a third embodiment of the present disclosure. FIG. **14** is a cross-sectional view taken along line XIV-XIV of FIG. **13**. The laminate **10A** includes the base material **11**, the adhesive layer **12**, the intermediate layer **16**, the adhesive layer **14**, the overlay layer **15**, and a recording medium **20A**. Note that, in the third embodiment, the parts similar to those in the first embodiment are denoted by the same reference numerals, and the description thereof will be omitted.

(132) (Intermediate Layer)

(133) The intermediate layer **16** can protect a side surface of the recording medium **20A**. The intermediate layer **16** surrounds a peripheral edge portion of one main surface of the base material **11**. The intermediate layer **16** has a frame shape in a plan view. In the present specification, the peripheral edge portion of one main surface refers to a region having a predetermined width from the peripheral edge of one main surface toward the inside. In addition, in the present specification, a plan view means a plan view when an object is viewed from a direction perpendicular to one main surface of the base material **11**.

(134) The intermediate layer **16** has an accommodation part **16A**. The recording medium **20A** is accommodated in the accommodation part **16A**. The accommodation part **16A** is a through hole penetrating in the thickness direction of the recording medium **20A**. The intermediate layer **16** and the recording medium **20A** preferably have substantially the same thickness. As a result, it is possible to suppress the formation of steps at the boundary between the intermediate layer **16** and the recording medium **20A** in a state where the recording medium **20A** is in the accommodation part **16A**.

(135) The intermediate layer **16** has a film shape. The intermediate layer **16** may have transparency. The intermediate layer **16** contains plastic. As the plastic, materials similar to those of the base

material **11** can be exemplified.

(136) (Recording Medium **20A**)

(137) FIG. **15** is a cross-sectional view of the recording medium **20A**. The recording medium **20A** includes the base material **21**, the pressure-sensitive adhesive layer **22**, the color development layer **24**, an intermediate layer **35A**, the color development layer **27**, an intermediate layer **35B**, the color development layer **30**, an intermediate layer **35C**, and a protective layer **36** in this order. More specifically, the recording medium **20A** includes the base material **21**, the pressure-sensitive adhesive layer **22**, the color development layer **24**, the heat insulating layer **26**, the pressure-sensitive adhesive layer **25**, the color development layer **27**, the heat insulating layer **29**, the pressure-sensitive adhesive layer **28**, the color development layer **30**, the heat insulating layer **34**, the pressure-sensitive adhesive layer **33**, and the protective layer **36** in this order. The heat insulating layers **26**, **29**, and **34** are provided as necessary, and thus are not necessarily provided. The recording medium **20A** is accommodated in the accommodation part **16A** of the intermediate layer **16** such that the base material **21** is on the adhesive layer **12** side and the protective layer **31** is on the adhesive layer **14** side.

(138) (Intermediate Layer)

(139) The intermediate layer **35A** is similar to the intermediate layer **32B** of the recording medium **20** except that the heat insulating layer **26** is adjacent to the color development layer **24** and the pressure-sensitive adhesive layer **25** is adjacent to the color development layer **27**. The intermediate layer **35B** is similar to the intermediate layer **32C** of the recording medium **20** except that the heat insulating layer **29** is adjacent to the color development layer **27** and the pressure-sensitive adhesive layer **28** is adjacent to the color development layer **30**. The intermediate layer **35C** is similar to the intermediate layer **32D** of the recording medium **20** except that the heat insulating layer **34** is adjacent to the color development layer **30** and the pressure-sensitive adhesive layer **33** is adjacent to the protective layer **36**.

(140) (Protective Layer **36**)

(141) The protective layer **36** includes an ultraviolet curable resin layer **36A**, a UV cut layer **36B**, a pressure-sensitive adhesive layer **36C**, and a base material **36D** in order on one main surface of the intermediate layer **35C**. The ultraviolet curable resin layer **36A** can protect the surface of the recording medium **20A**. The ultraviolet curable resin layer **36A** may have a function as a heat insulating layer and/or a diffusion preventing layer. The UV cut layer **36B** can cut ultraviolet rays incident on the color development layers **24**, **27**, and **30**.

(142) The pressure-sensitive adhesive layer **36C** can bond the UV cut layer **36B** and the base material **36D** to each other.

(143) As the material of the pressure-sensitive adhesive layer **36C**, materials similar to those of the pressure-sensitive adhesive layers **22**, **25**, and **28** can be exemplified. The base material **36D** can support the ultraviolet curable resin layer **36A**, the UV cut layer **36B**, and the pressure-sensitive adhesive layer **36C**. The base material **36D** can protect the surface of the recording medium **20A**. As the material of the base material **36D**, for example, materials similar to those of the base material **11** can be exemplified.

3.2 Action and Effect

(144) The laminate **10A** according to the third embodiment can provide an action and effect similar to those of the laminate **10** according to the first embodiment.

4 Fourth Embodiment

4.1 Configuration of Laminate

(145) FIG. **16** is a cross-sectional view of a laminate **40A** according to a fourth embodiment of the present disclosure. The laminate **40A** is different from the laminate **40** according to the second embodiment in that the laminate **40A** includes the intermediate layer **16** and the recording medium **20A** instead of the intermediate layer **13** and the recording medium **20** (see, FIG. **4**). The intermediate layer **16** and the recording medium **20A** are as described in the third embodiment.

4.2 Action and Effect

(146) The laminate **40A** according to the fourth embodiment can provide an action and effect similar to those of the laminate **40** according to the second embodiment.

5 Modification Examples

Modification Example 1

(147) In the first embodiment, an example in which the accommodation part **13A** is a through hole penetrating in the thickness direction of the intermediate layer **13** has been described. However, as illustrated in FIG. 5, the accommodation part **13A** may be a recess recessed in the thickness direction of the intermediate layer **13**. In this case, the recess may be provided on the main surface on the side facing the overlay layer **15** among both main surfaces of the intermediate layer **13**, or may be provided on the main surface on the side facing the base material **11**. Similarly, in the second embodiment, a recess may be provided as the accommodation part **13A** instead of the through hole. Similarly, in the third embodiment, as illustrated in FIG. 17, a recess may be provided as the accommodation part **16A** instead of the through hole. Similarly, in the fourth embodiment, a recess may be provided as an accommodation part **17A** instead of the through hole.

Modification Example 2

(148) In the first, second, third, and fourth embodiments, examples in which each of the laminates **10**, **40**, **10A**, and **40A** includes the recording medium **20** or **20A** including three color development layers (color development layers **24**, **27**, and **30**) developing colors of different hues from one another have been described, but these laminates may include a recording medium including a color development layer capable of performing multicolor display in a single layer structure.

(149) FIG. 6 is a cross-sectional view of a recording medium **50** that enables multicolor display even in a single layer structure. The recording medium **50** includes a base material **51**, a color development layer **52**, and a protective layer **53** in this order. The base material **51** and the protective layer **53** are similar to the base material **21** and the protective layer **31** in the first embodiment, respectively.

(150) The color development layer **52** includes three types of microcapsules **52C**, **52M**, and **52Y** developing colors of different hues from one another. That is, the color development layer **52** includes three types of microcapsules **52C**, **52M**, and **52Y** that exhibit different colors in the color development state. The color development layer **52** may contain a first matrix polymer as necessary. Each of the three types of microcapsules **52C**, **52M**, and **52Y** contains: for example, a coloring compound exhibiting different colors (for example, cyan (C), magenta, (M) and yellow (Y)); a developer corresponding to each of the coloring compounds; a photothermal conversion material that absorbs light in different wavelength ranges and generates heat; and a second matrix polymer. As the material of the microcapsule wall containing the above-described materials, for example, it is preferable to use materials similar to the materials constituting the heat insulating layers **23**, **26**, and **29**.

Modification Example 3

(151) In the first, second, third, and fourth embodiments, examples in which each of the recording media **20** and **20A** includes three color development layers (color development layers **24**, **27**, and **30**) have been described, but the recording media **20** and **20A** may include a single color development layer. In this case, the recording media **20** and **20A** may include a base material, a pressure-sensitive adhesive layer, a color development layer, and a protective layer in this order. The color development layer may exhibit black color in the color development state.

(152) Furthermore, the recording media **20** and **20A** may include the first color development layer to the nth color development layer (here, n is an integer of 2 or more). In this case, the first color development layer to the nth color development layer may contain coloring compounds developing colors of different hues from one another.

Modification Example 4

(153) In the first and second embodiments, the intermediate layer **13** may include a recording

medium capable of rewriting the pattern or the like by an external stimulus such as laser light or heat. More specifically, the intermediate layer **13** may include a recording medium capable of reversibly changing the colored state by an external stimulus such as laser light or heat. The recording medium may have a configuration capable of performing full-color recording, or may be capable of recording a single color such as monochrome.

Modification Example 5

(154) In the first, second, third, and fourth embodiments, the developer may contain a compound represented by the following Formula (3):

(155) ##STR00003## (where X^{sup.0} is a divalent group including at least one benzene ring, Y^{sup.01} and Y^{sup.02} are each independently a monovalent group, n₀₁ and n₀₂ are each independently an integer of 0 to 5, in a case where n₀₁ is an integer of 2 to 5, Y^{sup.01}s may be the same as or different from each other, in a case where n₀₂ is an integer of 2 to 5, Y^{sup.02}s may be the same as or different from each other, and Z^{sup.01} and Z^{sup.02} are each independently a hydrogen bonding group.)

(156) When X^{sup.0} includes at least one benzene ring, the melting point can be increased as compared with the case where X^{sup.0} is an aliphatic hydrocarbon group (for example, a normal alkyl chain), so that the color development retention characteristics (hereinafter, referred to as “high temperature and high humidity storage characteristics”) at the time of high temperature and high humidity storage can be improved. X^{sup.0} preferably includes at least two benzene rings, from the viewpoint of improving the high temperature and high humidity storage characteristics and heat resistance. The high temperature and high humidity storage characteristics are, for example, storage characteristics under an environment of 80° C. and 60% RH. When the heat resistance is improved, the resistance of the recording medium **20** against severe processes (for example, heat pressing, and integral molding using, for example, a molten resin or the like) is improved. In a case where X^{sup.0} includes at least two benzene rings, the at least two benzene rings may be condensed. For example, the condensed benzene rings may be naphthalene or anthracene, or the like.

(157) Since Z^{sup.01} and Z^{sup.02} are each independently a hydrogen bonding group, the developer is likely to exist in a state of being gathered to some extent via a hydrogen bond, so that the stability of the developer in the color development layers **24**, **27**, and **30** is improved. In the present specification, the hydrogen bonding group means a functional group including an atom that can be bonded to an atom present in another functional group, another compound, or the like via a hydrogen bond.

(158) The developer preferably contains a compound represented by the following Formula (4):

(159) ##STR00004## (where X^{sup.1} is a divalent group including at least one benzene ring, Y^{sup.11}, Y^{sup.12}, Y^{sup.13}, and Y^{sup.14} are each independently a monovalent group, and Z^{sup.11} and Z^{sup.12} are each independently a hydrogen bonding group.)

(160) When X^{sup.1} includes at least one benzene ring, the melting point can be increased as compared with the case where X^{sup.1} is an aliphatic hydrocarbon group (for example, a normal alkyl chain), so that the high temperature and high humidity storage characteristics can be improved. X^{sup.1} preferably includes at least two benzene rings, from the viewpoint of improving the high temperature and high humidity storage characteristics and heat resistance. In a case where X^{sup.1} includes at least two benzene rings, the at least two benzene rings may be condensed. For example, the condensed benzene rings may be naphthalene or anthracene, or the like.

(161) Since Z^{sup.11} and Z^{sup.12} are each independently a hydrogen bonding group, the developer is likely to exist in a state of being gathered to some extent via a hydrogen bond, so that the stability of the developer in the color development layers **24**, **27**, and **30** is improved.

(162) In a case where Formula (3) and Formula (4) include a hydrocarbon group, the hydrocarbon group is a generic term for groups including carbon (C) and hydrogen (H), and may be a saturated hydrocarbon group or an unsaturated hydrocarbon group. The saturated hydrocarbon group is an

aliphatic hydrocarbon group having no carbon-carbon multiple bond, and the unsaturated hydrocarbon group is an aliphatic hydrocarbon group having a carbon-carbon multiple bond (carbon-carbon double bond or carbon-carbon triple bond).

(163) In a case where Formula (3) and Formula (4) include a hydrocarbon group, the hydrocarbon group may be a chain or may contain one or two or more rings. The chain may be a linear chain, or may be a branched chain having one or more side chains, or the like.

(164) (X^{sup.0}, X^{sup.1} Including One Benzene Ring)

(165) X^{sup.0} in Formula (3) and X^{sup.1} in Formula (4) are, for example, a divalent group including one benzene ring. The divalent group is represented by, for example, the following Formula (5):

(166) ##STR00005## (where X^{sup.21} may or may not be present, in a case where X^{sup.21} is present, X^{sup.21} is a divalent group, X^{sup.22} may or may not be present, in a case where X^{sup.22} is present, X^{sup.22} is a divalent group, R^{sup.21} is a monovalent group, n₂₁ is an integer of 0 to 4, in a case where n₂₁ is an integer of 2 to 4, R^{sup.21}s may be the same as or different from each other, and the symbol “*” represents a bonding portion.)

(167) In Formula (5), the bonding positions of X^{sup.21} and X^{sup.22} to the benzene ring are not limited. That is, the bonding positions of X^{sup.21} and X^{sup.22} to the benzene ring may be any of an ortho position, a meta position, and a para position.

(168) The divalent group including one benzene ring is preferably represented by the following Formula (6) from the viewpoint of improving high temperature and high humidity storage characteristics:

(169) ##STR00006## (where R^{sup.22} is a monovalent group, n₂₂ is an integer of 0 to 4, in a case where n₂₂ is an integer of 2 to 4, R^{sup.22}s may be the same as or different from each other, and the symbol “*” represents a bonding portion.)

(170) In a case where X^{sup.0} in Formula (3) is a divalent group including one benzene ring, the bonding positions of Z^{sup.01} and Z^{sup.02} to the benzene ring in Formula (6) are not limited. That is, the bonding positions of Z^{sup.01} and Z^{sup.02} to the benzene ring may be any of an ortho position, a meta position, and a para position.

(171) In a case where X^{sup.1} in Formula (4) is a divalent group including one benzene ring, the bonding positions of Z^{sup.11} and Z^{sup.12} to the benzene ring in Formula (6) are not limited. That is, the bonding positions of Z^{sup.11} and Z^{sup.12} to the benzene ring may be any of an ortho position, a meta position, and a para position.

(172) (X^{sup.21}, X^{sup.22})

(173) X^{sup.21} and X^{sup.22} in Formula (5) may be each independently a divalent group, and are not particularly limited, but are exemplified as a hydrocarbon group optionally having a substituent. The hydrocarbon group is preferably a chain hydrocarbon group. When the hydrocarbon group is a chain hydrocarbon group, the melting point of the developer can be decreased, so that the developer is dissolved by irradiation with laser light, and the coloring compound is easily caused to develop color. From the viewpoint of decreasing the melting point of the developer, among the chain hydrocarbon groups, a normal alkyl chain is particularly preferable.

(174) The number of carbon atoms of the hydrocarbon group optionally having a substituent is, for example, 1 or more and 15 or less, 1 or more and 13 or less, 1 or more and 12 or less, 1 or more and 10 or less, 1 or more and 6 or less, or 1 or more and 3 or less.

(175) In a case where X^{sup.21} and X^{sup.22} in Formula (5) are a normal alkyl group, the number of carbon atoms of the normal alkyl group is preferably 8 or less, more preferably 6 or less, still more preferably 5 or less, and particularly preferably 3 or less from the viewpoint of high-temperature storage stability. It is considered that in a case where the number of carbon atoms of the normal alkyl group is 8 or less, the length of the normal alkyl group is short, so that thermal disturbance is less likely to occur in the developer during high-temperature storage, and a site interacting with the coloring compound such as the leuco dye at the time of color development is

less likely to be removed. Therefore, the coloring compound such as the leuco dye is hardly decolorized during high-temperature storage, and thus high-temperature storage stability is improved. (176) Examples of the substituent that is optionally included in the hydrocarbon group include halogen groups (for example, a fluorine group) or alkyl groups having a halogen group (for example, a fluorine group), and the like. The hydrocarbon group optionally having a substituent may be a hydrocarbon group in which a part of carbon of the hydrocarbon group (for example, a part of carbon included in the main chain of the hydrocarbon group) is substituted with an element such as oxygen.

(177) (R.sup.21)

(178) R.sup.21 in Formula (5) is not particularly limited as long as it is a monovalent group, and is, for example, a halogen group or a hydrocarbon group optionally having a substituent.

(179) The halogen group is, for example, a fluorine group (—F), a chlorine group (—Cl), a bromine group (—Br), or an iodine group (—I)

(180) The number of carbon atoms of the hydrocarbon group optionally having a substituent is, for example, 1 or more and 15 or less, 1 or more and 13 or less, 1 or more and 12 or less, 1 or more and 10 or less, 1 or more and 6 or less, or 1 or more and 3 or less.

(181) Examples of the substituent that is optionally included in the hydrocarbon group include halogen groups (for example, a fluorine group) or alkyl groups having a halogen group (for example, a fluorine group), and the like. The hydrocarbon group optionally having a substituent may be a hydrocarbon group in which a part of carbon of the hydrocarbon group (for example, a part of carbon included in the main chain of the hydrocarbon group) is substituted with an element such as oxygen.

(182) (R.sup.22)

(183) R.sup.22 in Formula (6) is not particularly limited as long as it is a monovalent group, and is, for example, a halogen group or a hydrocarbon group optionally having a substituent. The halogen group and the hydrocarbon group optionally having a substituent are each similar to R.sup.21 in Formula (3) described above.

(184) (X.sup.0, X.sup.1 Including Two Benzene Rings)

(185) X.sup.0 in Formula (3) and X.sup.1 in Formula (4) are, for example, a divalent group including two benzene rings. The divalent group is represented by, for example, the following Formula (7):

(186) ##STR00007## (where X.sup.31 may or may not be present, in a case where X.sup.31 is present, X.sup.31 is a divalent group, X.sup.32 may or may not be present, in a case where X.sup.32 is present, X.sup.32 is a divalent group, X.sup.33 may or may not be present, in a case where X.sup.33 is present, X.sup.33 is a divalent group, R.sup.31 and R.sup.32 are each independently a monovalent group, n₃₁ and n₃₂ are each independently an integer of 0 to 4, in a case where n₃₁ is an integer of 2 to 4, R.sup.31s may be the same as or different from each other, in a case where n₃₂ is an integer of 2 to 4, R.sup.32s may be the same as or different from each other, and the symbol “*” represents a bonding portion.)

(187) In Formula (7), the bonding positions of X.sup.31 and X.sup.32 to the benzene ring are not limited. That is, the bonding positions of X.sup.31 and X.sup.32 to the benzene ring may be any of an ortho position, a meta position, and a para position. Similarly, in Formula (7), the bonding positions of X.sup.32 and X.sup.33 to the benzene ring are not limited. That is, the bonding positions of X.sup.32 and X.sup.33 to the benzene ring may be any of an ortho position, a meta position, and a para position.

(188) The divalent group including two benzene rings is preferably represented by the following Formula (8) from the viewpoint of improving high temperature and high humidity storage characteristics:

(189) ##STR00008## (where X.sup.34 is a divalent group, R.sup.33 and R.sup.34 are each independently a monovalent group, n₃₃ and n₃₄ are each independently an integer of 0 to 4, in a

case where n³³ is an integer of 2 to 4, R^{33s} may be the same as or different from each other, in a case where n³⁴ is an integer of 2 to 4, R^{34s} may be the same as or different from each other, and the symbol “*” represents a bonding portion.)

(190) In a case where X⁰ in Formula (3) is a divalent group including two benzene rings, the bonding positions of Z⁰¹ and X³⁴ to the benzene ring in Formula (8) are not limited. That is, the bonding positions of Z⁰¹ and X³⁴ to the benzene ring may be any of an ortho position, a meta position, and a para position. Similarly, in Formula (8), the bonding positions of Z⁰² and X³⁴ to the benzene ring are not limited. That is, the bonding positions of Z⁰² and X³⁴ to the benzene ring may be any of an ortho position, a meta position, and a para position.

(191) In a case where X¹ in Formula (4) is a divalent group including two benzene rings, the bonding positions of Z¹¹ and X³⁴ to the benzene ring in Formula (8) are not limited. That is, the bonding positions of Z¹¹ and X³⁴ to the benzene ring may be any of an ortho position, a meta position, and a para position. Similarly, in Formula (8), the bonding positions of Z¹² and X³⁴ to the benzene ring are not limited. That is, the bonding positions of Z¹² and X³⁴ to the benzene ring may be any of an ortho position, a meta position, and a para position.

(192) (X³¹, X³², X³³)

(193) X³¹, X³², and X³³ in Formula (7) may be each independently a divalent group, and are not particularly limited, but are, for example, a hydrocarbon group optionally having a substituent. The hydrocarbon group is similar to X²¹ and X²² in Formula (5) described above.

(194) (X³⁴)

(195) X³⁴ in Formula (8) is not particularly limited as long as it is a divalent group, but is, for example, a hydrocarbon group optionally having a substituent. The hydrocarbon group is similar to X²¹ and X²² in Formula (5) described above.

(196) (R³¹, R³²)

(197) R³¹ and R³² in Formula (7) are not particularly limited as long as they are a monovalent group, and are, for example, a halogen group or a hydrocarbon group optionally having a substituent. The halogen group and the hydrocarbon group optionally having a substituent are each similar to R²¹ in Formula (5) described above.

(198) (R³³, R³⁴)

(199) R³³ and R³⁴ in Formula (8) are not particularly limited as long as they are a monovalent group, and are, for example, a halogen group or a hydrocarbon group optionally having a substituent. The halogen group and the hydrocarbon group optionally having a substituent are each similar to R²¹ in Formula (5) described above.

(200) (Y⁰¹, Y⁰²)

(201) Y⁰¹ and Y⁰² in Formula (3) are each independently, for example, a hydrogen group (—H), a hydroxy group (—OH), a halogen group (—X), a carboxy group (—COOH), an ester group (—COOR), or a hydrocarbon group optionally having a substituent.

(202) The halogen group is, for example, a fluorine group (—F), a chlorine group (—Cl), a bromine group (—Br), or an iodine group (—I)

(203) The number of carbon atoms of the hydrocarbon group optionally having a substituent is, for example, 1 or more and 15 or less, 1 or more and 13 or less, 1 or more and 12 or less, 1 or more and 10 or less, 1 or more and 6 or less, or 1 or more and 3 or less.

(204) Examples of the substituent that is optionally included in the hydrocarbon group include halogen groups (for example, a fluorine group) or alkyl groups having a halogen group (for example, a fluorine group), and the like. The hydrocarbon group optionally having a substituent may be a hydrocarbon group in which a part of carbon of the hydrocarbon group (for example, a part of carbon included in the main chain of the hydrocarbon group) is substituted with an element

such as oxygen.

(205) In Formula (3), one of (Y^{sup.01}).sub.n01 and/or one of (Y^{sup.02}).sub.n02 is preferably a hydroxy group (—OH). When one of (Y^{sup.01}).sub.n01 and/or one of (Y^{sup.02}).sub.n02 is a hydroxy group (—OH), display quality and light resistance can be improved.

(206) (Y^{sup.11}, Y^{sup.12}, Y^{sup.13}, Y^{sup.14})

(207) In Formula (4), the bonding positions of Y^{sup.11} and Y^{sup.12} to the benzene ring are not limited. That is, the bonding positions of Y^{sup.11} and Y^{sup.12} to the benzene ring may be any of an ortho position, a meta position, and a para position. Similarly, in Formula (4), the bonding positions of Y^{sup.13} and Y^{sup.14} to the benzene ring are also not limited. That is, the bonding positions of Y^{sup.13} and Y^{sup.14} to the benzene ring may be any of an ortho position, a meta position, and a para position. In Formula (4), the bonding positions of Y^{sup.11} and Y^{sup.12} to one benzene and the bonding positions of Y^{sup.13} and Y^{sup.14} to the other benzene may be the same or different.

(208) Y^{sup.11}, Y^{sup.12}, Y^{sup.13}, and Y^{sup.14} in Formula (4) each independently represent, for example, a hydrogen group (—H), a hydroxy group (—OH), a halogen group, a carboxy group (—COOH), an ester group (—COOR), or a hydrocarbon group optionally having a substituent. The halogen group and the hydrocarbon group optionally having a substituent are each similar to Y^{sup.01} and Y^{sup.02} in Formula (3) described above.

(209) In Formula (4), Y^{sup.11} and/or Y^{sup.13} are preferably a hydroxy group (—OH). When Y^{sup.11} and/or Y^{sup.13} is a hydroxy group (—OH), display quality and light resistance can be improved.

(210) (Z^{sup.01}, Z^{sup.02})

(211) Z^{sup.01} and Z^{sup.02} in Formula (3) are each independently, for example, a urea bond (—NHCONH—), an amide bond (—NHCO—, —OCHN—), or a hydrazide bond (—NHCOCONH—). Z^{sup.01} and Z^{sup.02} are preferably a urea bond from the viewpoint of improving high temperature and high humidity storage characteristics. In a case where Z^{sup.01} is an amide bond, the nitrogen contained in the amide bond may be bonded to benzene, or the carbon contained in the amide bond may be bonded to benzene. In a case where Z^{sup.02} is an amide bond, the nitrogen contained in the amide bond may be bonded to benzene, or the carbon contained in the amide bond may be bonded to benzene.

(212) (Z^{sup.11}, Z^{sup.12})

(213) Z^{sup.11} and Z^{sup.12} in Formula (4) are each independently, for example, a urea bond (—NHCONH—), an amide bond (—NHCO—, —OCHN—), or a hydrazide bond (—NHCOCONH—). Z^{sup.11} and Z^{sup.12} are preferably a urea bond from the viewpoint of improving high temperature and high humidity storage characteristics. In a case where Z^{sup.11} is an amide bond, the nitrogen contained in the amide bond may be bonded to benzene, or the carbon contained in the amide bond may be bonded to benzene. In a case where Z^{sup.12} is an amide bond, the nitrogen contained in the amide bond may be bonded to benzene, or the carbon contained in the amide bond may be bonded to benzene.

Specific Examples of Developer

(214) Specifically, a developer, in which X^{sup.0} in Formula (3) and X^{sup.1} in Formula (4) include one benzene ring, contains, for example, at least one selected from the group consisting of compounds represented by the following Formulas (9-1) to (9-6).

(215) ##STR00009##

(216) Specifically, a developer, in which X^{sup.0} in Formula (3) and X^{sup.1} in Formula (4) include two benzene rings, contains, for example, at least one selected from the group consisting of compounds represented by the following Formulas (10-1) to (10-8).

(217) ##STR00010##

Modification Example 6

(218) In the first embodiment, an example in which the laminate **10** includes the recording medium

20 (see, FIG. 3) has been described, but the laminate **10** may include a recording medium **20B** illustrated in FIG. 18 instead of the recording medium **20**. The recording medium **20B** is different from the recording medium **20** in that the recording medium **20B** includes the protective layer **36** instead of the protective layer **31**. The protective layer **36** is as described in the third embodiment. Similarly in the second embodiment, the laminate **40** may include the recording medium **20B** illustrated in FIG. 18 instead of the recording medium **20**.

Modification Example 7

(219) In the third embodiment, an example in which the laminate **10A** includes the recording medium **20A** has been described, but the laminate **10A** may include a recording medium **20C** illustrated in FIG. 19 instead of the recording medium **20A** (see, FIG. 15). The recording medium **20C** is different from the recording medium **20A** in that the recording medium **20C** includes intermediate layers **37A**, **37B**, and **37C** instead of the intermediate layers **35A**, **35B**, and **35C**. The recording medium **20C** does not necessarily include the base material **21** and the pressure-sensitive adhesive layer **22**.

(220) The intermediate layer **37A** includes a heat insulating layer **26A** and the pressure-sensitive adhesive layer **25** in order on one main surface of the color development layer **24**. The heat insulating layer **26A** includes a resin layer **26A1** and an ultraviolet curable resin layer **26A2** in order on one main surface of the color development layer **24**. The resin layer **26A1** is provided between the color development layer **24** and the ultraviolet curable resin layer **26A2**. The resin layer **26A1** can improve the adhesion between the color development layer **24** and the ultraviolet curable resin layer **26A2**. The resin layer **26A1** contains the same type of resin material as the matrix polymer contained in the color development layer **24**. For example, in a case where the color development layer **24** contains a polycarbonate-based resin as a matrix polymer, the resin layer **26A1** contains a polycarbonate-based resin. The ultraviolet curable resin layer **26A2** is similar to the ultraviolet curable resin layer of the heat insulating layer **26** in the third embodiment.

(221) The intermediate layer **37B** includes a heat insulating layer **29A** and the pressure-sensitive adhesive layer **28** in order on one main surface of the color development layer **27**. The heat insulating layer **29A** includes a resin layer **29A1** and an ultraviolet curable resin layer **29A2** in order on one main surface of the color development layer **27**. The resin layer **29A1** is provided between the color development layer **27** and the ultraviolet curable resin layer **29A2**. The resin layer **29A1** can improve the adhesion between the color development layer **27** and the ultraviolet curable resin layer **29A2**. The resin layer **29A1** contains the same type of resin material as the matrix polymer contained in the color development layer **27**. For example, in a case where the color development layer **27** contains a polycarbonate-based resin as a matrix polymer, the resin layer **29A1** contains a polycarbonate-based resin. The ultraviolet curable resin layer **29A2** is similar to the ultraviolet curable resin layer of the heat insulating layer **29** in the third embodiment.

(222) The intermediate layer **37C** includes a heat insulating layer **34A** and the pressure-sensitive adhesive layer **33** in order on one main surface of the color development layer **30**.

(223) The heat insulating layer **34A** includes a resin layer **34A1** and an ultraviolet curable resin layer **34A2** in order on one main surface of the color development layer **30**. The resin layer **34A1** is provided between the color development layer **30** and the ultraviolet curable resin layer **34A2**. The resin layer **34A1** can improve the adhesion between the color development layer **30** and the ultraviolet curable resin layer **34A2**. The resin layer **34A1** contains the same type of resin material as the matrix polymer contained in the color development layer **30**. For example, in a case where the color development layer **30** contains a polycarbonate-based resin as a matrix polymer, the resin layer **34A1** contains a polycarbonate-based resin. The ultraviolet curable resin layer **34A2** is similar to the ultraviolet curable resin layer of the heat insulating layer **34** in the third embodiment.

(224) The reason why the resin layer **26A1** is provided between the color development layer **24** and the ultraviolet curable resin layer **26A2** is as follows. In a case where the color development layer **24** contains a particulate developer, the particulate developer is distributed on the surface of the

color development layer **24**. Therefore, in a case where the color development layer **24** and the ultraviolet curable resin layer **26A2** are adjacent to each other, the adhesion may be reduced. As described above, since the resin layer **34A1** is adjacent to the color development layer **24** and the resin layer **34A1** contains the same type of resin material as the matrix polymer contained in the color development layer **24**, the adhesion at the interface other than the portion where the developer is distributed can be improved. Therefore, it is possible to compensate for a decrease in adhesion due to the particulate developer.

(225) The reason why the resin layer **29A1** is provided between the color development layer **27** and the ultraviolet curable resin layer **29A2** and the reason why the resin layer **34A1** is provided between the color development layer **30** and the ultraviolet curable resin layer **34A2** are similar to the reason why the resin layer **26A1** is provided between the color development layer **24** and the ultraviolet curable resin layer **26A2**.

Modification Example 8

(226) In the third embodiment, an example in which the laminate **10A** includes the recording medium **20A** has been described, but the laminate **10A** may include a recording medium **20D** illustrated in FIG. **20** instead of the recording medium **20A** (see, FIG. **15**). The recording medium **20D** is different from the recording medium **20A** in that the recording medium **20D** includes intermediate layers **38A**, **38B**, and **38C** instead of the intermediate layers **35A**, **35B**, and **35C**.

(227) The intermediate layer **38A** includes a heat insulating layer **26B** and the pressure-sensitive adhesive layer **25** in order on one main surface of the color development layer **24**.

(228) The heat insulating layer **26B** includes a pressure-sensitive adhesive layer **26B1** and an ultraviolet curable resin layer **26B2** in order on one main surface of the color development layer **24**. The pressure-sensitive adhesive layer **26B1** is provided between the color development layer **24** and the ultraviolet curable resin layer **26B2**. The pressure-sensitive adhesive layer **26B1** can bond the color development layer **24** and the ultraviolet curable resin layer **26B2** to each other. Since the pressure-sensitive adhesive layer **26B1** is provided between the color development layer **24** and the ultraviolet curable resin layer **26B2**, it is possible to compensate for a decrease in adhesive force due to the developer contained in the color development layer **24**. As the material of the pressure-sensitive adhesive layer **26B1**, materials similar to those of the pressure-sensitive adhesive layers **22**, **25**, and **28** can be exemplified.

(229) The intermediate layer **38B** includes a heat insulating layer **29B** and the pressure-sensitive adhesive layer **28** in order on one main surface of the color development layer **27**.

(230) The heat insulating layer **29B** includes a pressure-sensitive adhesive layer **29B1** and an ultraviolet curable resin layer **29B2** in order on one main surface of the color development layer **27**. The pressure-sensitive adhesive layer **29B1** is provided between the color development layer **27** and the ultraviolet curable resin layer **29B2**. The pressure-sensitive adhesive layer **29B1** can bond the color development layer **27** and the ultraviolet curable resin layer **29B2** to each other. Since the pressure-sensitive adhesive layer **29B1** is provided between the color development layer **27** and the ultraviolet curable resin layer **29B2**, it is possible to compensate for a decrease in adhesive force due to the developer contained in the color development layer **27**. As the material of the pressure-sensitive adhesive layer **29B1**, materials similar to those of the pressure-sensitive adhesive layers **22**, **25**, and **28** can be exemplified.

(231) The intermediate layer **38C** includes a heat insulating layer **34B** and the pressure-sensitive adhesive layer **33** in order on one main surface of the color development layer **30**.

(232) The heat insulating layer **34B** includes a pressure-sensitive adhesive layer **34B1** and an ultraviolet curable resin layer **34B2** in order on one main surface of the color development layer **30**. The pressure-sensitive adhesive layer **34B1** is provided between the color development layer **30** and the ultraviolet curable resin layer **34B2**. The pressure-sensitive adhesive layer **34B1** can bond the color development layer **30** and the ultraviolet curable resin layer **34B2** to each other. Since the pressure-sensitive adhesive layer **34B1** is provided between the color development layer **30** and the

ultraviolet curable resin layer **34B2**, it is possible to compensate for a decrease in adhesive force due to the developer contained in the color development layer **30**. As the material of the pressure-sensitive adhesive layer **34B1**, materials similar to those of the pressure-sensitive adhesive layers **22**, **25**, and **28** can be exemplified.

Modification Example 9

(233) In the third embodiment, an example in which the laminate **10A** includes the recording medium **20A** has been described, but the laminate **10A** may include a recording medium **20E** illustrated in FIG. **21** instead of the recording medium **20A** (see, FIG. **15**). The recording medium **20E** is different from the recording medium **20A** in that the recording medium **20E** includes intermediate layers **39A**, **39B**, and **39C** instead of the intermediate layers **35A**, **35B**, and **35C**. The recording medium **20E** does not necessarily include the base material **21** and the pressure-sensitive adhesive layer **22**.

(234) The intermediate layers **39A** and **39B** are a film. The film is preferably a film subjected to easy adhesion treatment. As the material of the film, materials similar to those of the base material **11** can be exemplified. Examples of the easy adhesion treatment include primer treatment, active energy ray irradiation treatment, plasma treatment, corona treatment, vapor deposition treatment, etching treatment, sandblast treatment, and the like. One or a combination of two or more can be selected from these treatments. The primer treatment may be primer treatment with a resin, a silane coupling agent, tetraalkoxysilane, or the like.

(235) Since the film subjected to easy adhesion treatment is provided as the intermediate layer **39A** between the color development layer **24** and the color development layer **27**, it is possible to compensate for a decrease in adhesion due to the developer contained in the color development layer **24**. Since the film subjected to easy adhesion treatment is provided as the intermediate layer **39B** between the color development layer **27** and the color development layer **30**, it is possible to compensate for a decrease in adhesion due to the developer contained in the color development layer **27**.

(236) The intermediate layer **39C** is a pressure-sensitive adhesive layer. As the material of the pressure-sensitive adhesive layer, materials similar to those of the pressure-sensitive adhesive layers **22**, **25**, and **28** can be exemplified. Since the pressure-sensitive adhesive layer is provided as the intermediate layer **39C** between the color development layer **30** and the protective layer **36**, it is possible to compensate for a decrease in adhesion due to the developer contained in the color development layer **30**.

Modification Example 10

(237) In the third embodiment, an example in which the laminate **10A** includes the recording medium **20A** has been described, but the laminate **10A** may include a recording medium **20F** illustrated in FIG. **22** instead of the recording medium **20A** (see, FIG. **15**). The recording medium **20F** is different from the recording medium **20E** in Modification Example 9 in that the recording medium **20F** includes an intermediate layer **41B** instead of the intermediate layer **39B**.

(238) The intermediate layer **41B** includes a resin layer **41B1** and a resin layer **41B2** in order on one main surface of the color development layer **27**. The resin layer **41B1** contains the same type of resin material as the matrix polymer contained in the color development layer **27**. For example, in a case where the color development layer **27** contains a polycarbonate-based resin as a matrix polymer, the resin layer **41B1** contains a polycarbonate-based resin. The resin layer **41B2** is a film. The film is preferably a film subjected to easy adhesion treatment. As the material of the film, materials similar to those of the base material **11** can be exemplified.

(239) As described above, since the resin layer **41B1** is provided between the color development layer **27** and the resin layer **41B2**, it is possible to compensate for a decrease in adhesion due to the developer contained in the color development layer **27**.

Modification Example 11

(240) In the third embodiment, an example in which the laminate **10A** includes the recording

medium **20A** has been described, but the laminate **10A** may include a recording medium **20G** illustrated in FIG. **23** instead of the recording medium **20A** (see, FIG. **15**). The recording medium **20G** is different from the recording medium **20E** in Modification Example 9 in that the recording medium **20G** includes the intermediate layer **38A** instead of the intermediate layer **39A**, and includes a base material **42**.

(241) The intermediate layer **38A** is as described in Modification Example 8 (see, FIG. **20**). The base material **42** is provided adjacent to the other surface of the color development layer **24**. The base material **42** is a film subjected to easy adhesion treatment. As the material of the film, materials similar to those of the base material **11** can be exemplified.

Modification Example 12

(242) In the third embodiment, an example in which the laminate **10A** includes the recording medium **20A** has been described, but the laminate **10A** may include a recording medium **20H** illustrated in FIG. **24** instead of the recording medium **20A** (see, FIG. **15**). The recording medium **20H** is different from the recording medium **20A** in that the recording medium **20H** includes intermediate layers **42A** and **42B** instead of the intermediate layers **35A** and **35B**.

(243) The intermediate layers **42A** and **42B** are a pressure-sensitive adhesive layer. As the material of the pressure-sensitive adhesive layer, materials similar to those of the pressure-sensitive adhesive layers **22**, **25**, and **28** can be exemplified.

Modification Example 13

(244) In the first and second embodiments, examples in which the laminate **10** includes the recording medium **20** have been described, but the laminate **10** may include the recording medium **20A** instead of the recording medium **20**.

Modification Example 14

(245) In the third and fourth embodiments, examples in which the laminate **10A** includes the recording medium **20A** have been described, but the laminate **10A** may include the recording medium **20** instead of the recording medium **20A**.

Modification Example 15

(246) In Modification Examples 7, 8, 9, 10, 11, and 12 described above, examples in which the laminate **10A** according to the third embodiment includes any one of the recording media **20C**, **20D**, **20E**, **20F**, **20G**, and **20H** instead of the recording medium **20A** have been described, but the present disclosure is not limited thereto. For example, the laminate **10** according to the first embodiment may include any one of the recording media **20C**, **20D**, **20E**, **20F**, **20G**, and **20H** instead of the recording medium **20**. The laminate **40** according to the second embodiment may include any one of the recording media **20C**, **20D**, **20E**, **20F**, **20G**, and **20H** instead of the recording medium **20**. The laminate **40A** according to the fourth embodiment may include any one of the recording media **20C**, **20D**, **20E**, **20F**, **20G**, and **20H** instead of the recording medium **20A**.

Modification Example 16

(247) In the first, second, third, and fourth embodiments and the modification examples thereof, examples in which the laminates **10**, **40**, **10A**, and **40A** are applied to cards have been described, but the laminates **10**, **40**, **10A**, and **40A** may be applied to housings of medical supplies, automobile parts, automobiles, toys, foods, cosmetics, clothing items, documents (for example, passport and the like), exterior components, electronic devices, and the like. Specific examples of the exterior component include an interior or exterior of a wall and the like of a building, an exterior of furniture such as a desk and the like. Specific examples of the electronic device include personal computers (hereinafter referred to as “PC”), mobile devices, mobile phones (for example, a smartphone), tablet computers, display apparatuses, imaging apparatuses, audio devices, game devices, industrial devices, medical devices, robots, wearable terminals, and the like. Specific examples of the wearable terminal include clothing items such as watches (wristwatches), bags, clothes, hats, glasses, and shoes.

(248) Hereinafter, specific examples in which the laminates **10**, **40**, **10A**, and **40A** are applied to a

smartphone, a notebook personal computer, and a decorative container will be described.

Example of Smartphone

(249) FIG. 7A illustrates an external configuration of the front surface of a smartphone **100**, and FIG. 7B illustrates an external configuration of the back surface of the smartphone **100** illustrated in FIG. 7A. The smartphone **100** includes, for example, a display part **111** and a housing **112**. The recording medium **20** is provided on the back side of the housing **112**. The housing **112** includes a laminate. This laminate is similar to any one of the laminates **10**, **40**, **10A**, and **40A** according to the first, second, third, and fourth embodiments and the modification examples thereof except that the base material has a housing shape of the smartphone **100**. Accordingly, the forgery preventing property and the like of the smartphone **100** can be improved.

Example of Notebook PC

(250) FIG. 8 illustrates an external configuration of a notebook PC **200**. The notebook PC **200** includes a computer main body **210** and a display **220**. The computer main body **210** includes a housing **211**, a keyboard **212**, a wheel/pad operation part **213**, and click buttons **214** and **215**. The housing **211** is provided with the recording medium **20**. The housing **211** includes a laminate. This laminate is similar to any one of the laminates **10**, **40**, **10A**, and **40A** according to the first, second, third, and fourth embodiments and the modification examples thereof except that the base material has a housing shape of the notebook PC **200**. Accordingly, the forgery preventing property and the like of the notebook PC **200** can be improved.

Example of Decorative Container

(251) FIG. 9 illustrates an appearance of a decorative container **300**. The decorative container **300** includes an accommodation part **311** and a lid **312** that covers the accommodation part **311**. The lid **312** is provided with the recording medium **20**. The lid **312** includes a laminate. This laminate is similar to any one of the laminates **10**, **40**, **10A**, and **40A** according to the first, second, third, and fourth embodiments and the modification examples thereof except that the base material has a shape corresponding to the lid **312**. Accordingly, the forgery preventing property and the like of the decorative container **300** can be improved.

Example of Passport

(252) FIG. 25 illustrates an appearance of a booklet **400**. The booklet **400** is a passport. The passport is an example of a booklet-type identification card. The booklet **400** includes a plurality of sheets **410**. The plurality of sheets **410** is saddle-stitched. The recording medium **20** and the like are provided on at least one surface or both surfaces of the sheet **410**. A face photograph or the like is drawn on the recording medium **20** and the like. The sheet **410** is similar to any one of the laminates **10**, **40**, **10A**, and **40A** according to the first, second, third, and fourth embodiments and the modification examples thereof. In this case, the base material **11** may be paper or the like.

(253) Although the embodiments and modification examples of the present disclosure have been specifically described above, the present disclosure is not limited to the embodiments and modification examples described above, and various modifications based on the technical idea of the present disclosure are possible.

(254) For example, the configurations, methods, processes, shapes, materials, numerical values, and the like described in the embodiments and modification examples described above are merely examples, and different configurations, methods, processes, shapes, materials, numerical values, and the like may be used as necessary. The configurations, methods, processes, shapes, materials, numerical values, and the like of the embodiments and modification examples described above can be combined with each other without departing from the gist of the present disclosure.

(255) In the numerical range described in stages in the embodiments and modification examples described above, the upper limit or the lower limit of the numerical range of a certain stage may be replaced with the upper limit or the lower limit of the numerical range of another stage. The materials exemplified in the embodiments and modification examples described above can be used alone or in combination of two or more unless otherwise specified.

(256) Furthermore, the present disclosure can adopt the following configurations.

(257) (1)

(258) A laminate including: a base material; an intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the intermediate layer, in which the accommodation part is provided in a part of a plane of the intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the intermediate layer or a recess recessed in a thickness direction of the intermediate layer, the recording medium is configured to be capable of changing a colored state by an external stimulus, and the base material and the intermediate layer are bonded to each other by fusion or a thermal adhesive, and the intermediate layer and the overlay layer are bonded to each other by fusion or a thermal adhesive.

(2)

(259) The laminate according to (1), in which the thermal adhesive contains a thermosetting resin.

(260) (3)

(261) The laminate according to (1), in which the base material and the intermediate layer are fused, and the intermediate layer and the overlay layer are fused, and the base material, the intermediate layer, and the overlay layer contain a thermoplastic resin.

(4)

(262) The laminate according to any one of (1) to (3), in which the recording medium is fitted in the accommodation part.

(263) (5)

(264) The laminate according to any one of (1) to (4), in which the external stimulus is laser light.

(265) (6)

(266) The laminate according to any one of (1) to (5), in which a change in the colored state is an irreversible change.

(267) (7)

(268) The laminate according to any one of (1) to (6), in which the recording medium includes a first color development layer to an nth color development layer, (provided that, n is an integer of 2 or more), and the first color development layer to the nth color development layer contain coloring compounds developing colors of different hues from one another.

(8)

(269) The laminate according to any one of (1) to (6), in which the recording medium includes a first color development layer, a second color development layer, and a third color development layer, and the first color development layer, the second color development layer, and the third color development layer contain coloring compounds developing colors of different hues from one another.

(9)

(270) The laminate according to any one of (1) to (6), in which the recording medium includes a color development layer containing three types of microcapsules developing colors of different hues from one another.

(271) (10)

(272) The laminate according to any one of (1) to (6), in which the recording medium includes a color development layer, and the color development layer contains: a coloring compound having an electron donating property; a developer having an electron accepting property; and a photothermal conversion material.

(11)

(273) A card including the laminate according to any one of (1) to (10).

(274) (12)

(275) A housing including the laminate according to any one of (1) to (10).

(276) Furthermore, the present disclosure can adopt the following configurations.

(277) (21)

(278) A laminate including: a base material; a first intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the first intermediate layer, in which the accommodation part is provided in a part of a plane of the first intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the first intermediate layer or a recess recessed in a thickness direction of the first intermediate layer, the recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin, the base material, the first intermediate layer, and the overlay layer contain the same type of resin material, and the base material and the first intermediate layer are bonded to each other by fusion, and the first intermediate layer and the overlay layer are bonded to each other by fusion.

(22)

(279) A laminate including: a base material; a first intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the first intermediate layer, in which the accommodation part is provided in a part of a plane of the first intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the first intermediate layer or a recess recessed in a thickness direction of the first intermediate layer, the recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin, the base material, the first intermediate layer, and the overlay layer contain the same type of resin material, and the base material and the first intermediate layer are bonded to each other by a thermal adhesive, and the first intermediate layer and the overlay layer are bonded to each other by a thermal adhesive.

(23)

(280) The laminate according to (21) or (22), in which the resin material contains a thermoplastic resin.

(281) (24)

(282) The laminate according to (21) or (22), in which the resin material contains a polycarbonate-based resin.

(283) (25)

(284) The laminate according to (21) or (22), in which the resin material contains a polyethylene terephthalate-based resin.

(285) (26)

(286) The laminate according to (22), in which the thermal adhesive contains a thermosetting resin.

(287) (27)

(288) The laminate according to any one of (21) to (26), in which the color development layer is configured to be capable of changing a colored state by laser light, and a change in the colored state is an irreversible change.

(28)

(289) The laminate according to any one of (21) to (27), in which the color development layer further contains a photothermal conversion material.

(290) (29)

(291) The laminate according to any one of (21) to (28), in which the recording medium includes a plurality of the color development layers, and the plurality of color development layers contain coloring compounds developing colors of different hues from one another.

(30)

(292) The laminate according to any one of (21) to (28), in which the recording medium includes a plurality of the color development layers and a plurality of second intermediate layers, and each of the plurality of second intermediate layers is provided between the color development layers

adjacent to each other.

(31)

(293) The laminate according to (30), in which at least one of the plurality of second intermediate layers includes an ultraviolet curable resin layer and a pressure-sensitive adhesive layer.

(294) (32)

(295) The laminate according to (30), in which at least one of the plurality of second intermediate layers includes a resin layer, an ultraviolet curable resin layer, and a pressure-sensitive adhesive layer, the ultraviolet curable resin layer is provided between the resin layer and the pressure-sensitive adhesive layer, and the resin layer contains a resin material of the same type as the matrix resin.

(33)

(296) The laminate according to (30), in which at least one of the plurality of second intermediate layers includes a first pressure-sensitive adhesive layer, an ultraviolet curable resin layer, and a second pressure-sensitive adhesive layer in order.

(297) (34)

(298) The laminate according to (30), in which at least one of the plurality of second intermediate layers is a film subjected to easy adhesion treatment.

(299) (35)

(300) The laminate according to any one of (21) to (28), in which the recording medium includes a plurality of the color development layers, a plurality of second intermediate layers, and a protective layer, the plurality of color development layers includes a first color development layer, a second color development layer, and a third color development layer, the first color development layer, the second intermediate layer, the second light emitting layer, the second intermediate layer, the third color development layer, the second intermediate layer, and the protective layer are laminated in this order, and the first color development layer, the second color development layer, and the third color development layer contain coloring compounds developing colors of different hues from one another.

(36)

(301) The laminate according to any one of (21) to (35), in which a proportion of the developer in a total amount of the developer and the matrix resin is 16 mass % or less.

(302) (37)

(303) A card including the laminate according to any one of (21) to (36).

(304) (38)

(305) A housing including the laminate according to any one of (21) to (36).

6 Reference Examples and Examples

(306) Hereinafter, the present disclosure will be specifically described with reference examples and examples, but the present disclosure is not limited to these reference examples and examples.

Reference Example 1-1

(307) First, a first adhesive layer was disposed on a base material, and then an intermediate layer was disposed on the first adhesive layer. Next, a second adhesive layer was disposed on the intermediate layer, and then an overlay layer was disposed on the second adhesive layer to obtain a laminated structure. Next, the laminated structure was heated and pressurized at a temperature of 120° C. to bond the base material and the intermediate layer to each other with the first adhesive layer interposed therebetween, and to bond the intermediate layer and the overlay layer to each other with the second adhesive layer interposed therebetween. As described above, an intended laminate was obtained.

(308) As the base material, the first adhesive layer, the intermediate layer, the second adhesive layer, and the overlay layer, the following materials were used. Overlay layer: 50 μm -thick polycarbonate film (hereinafter, referred to as "PC film") Second intermediate layer: 5 μm -thick epoxy-based resin layer (thermosetting resin layer) Intermediate layer: 100 μm -thick PC film First

adhesive layer: 5 μm -thick epoxy-based resin layer (thermosetting resin layer) Base material: 25 μm -thick PC film

Reference Example 1-2

(309) A laminate was obtained in a similar manner to Reference 1-1, except that the followings were used as the base material, the intermediate layer, and the overlay layer. Overlay layer: 50 μm -thick polyvinyl chloride film (hereinafter, referred to as "PVC film") Intermediate layer: 100 μm -thick PVC vinyl film Base material: 25 μm -thick PVC vinyl film

Reference Example 1-3

(310) A laminate was obtained in a similar manner to Reference 1-1, except that the followings were used as the base material, the intermediate layer, and the overlay layer. Overlay layer: 50 μm -thick polyethylene terephthalate film (hereinafter, referred to as "PET film") Intermediate layer: 100 μm -thick PET film Base material: 25 μm -thick PET film

Reference Example 1-4

(311) A laminate was obtained in a similar manner to Reference 1-1, except that the followings were used as the base material, the intermediate layer, and the overlay layer. Overlay layer: 50 μm -thick PC film Intermediate layer: 100 μm -thick PVC film Base material: 25 μm -thick PC film

Reference Examples 2-1, 2-2, 2-3, 2-4

(312) Laminates were obtained in a similar manner to Reference Examples 1-1, 1-2, 1-3, and 1-4, except that the base material, the intermediate layer, and the overlay layer were sequentially laminated to obtain a laminated structure, and then the laminated structure was heated and pressurized at a temperature of 180° C. to fuse the base material and the intermediate layer and fuse the intermediate layer and the overlay layer.

(313) [Evaluation]

(314) The adhesion, environmental consideration, and durability of the laminates obtained as described above were evaluated as follows.

(315) (Adhesion)

(316) First, the average peel strength between the base material and the intermediate layer and the average peel strength between the intermediate layer and the overlay layer were measured. The average peel strength was measured by the method for measuring the average peel strength of the laminate described in the first embodiment. Next, the measured average peel strength was evaluated according to the following criteria. The evaluation results are shown in Table 1. ○: The average peel strength between the base material and the intermediate layer and the average peel strength between the intermediate layer and the overlay layer are both 5.0 N/cm or more. ◦: The average peel strength between the base material and the intermediate layer and the average peel strength between the intermediate layer and the overlay layer are both 3.5 N/cm or more. x: The average peel strength between the base material and the intermediate layer and the average peel strength between the intermediate layer and the overlay layer are both less than 3.5 N/cm.

(Environmental Consideration)

(317) The environmental consideration of the laminate was evaluated according to the following criteria. The evaluation results are shown in Table 1. ◦: There is no possibility that harmful substances (particularly, dioxin) are generated when the laminate is treated with insufficient equipment. x: There is a possibility that harmful substances (particularly, dioxin) are generated when the laminate is treated with insufficient equipment.

(Durability)

(318) In accordance with ISO/IEC 10373-1, the durability of the laminate was evaluated according to the following criteria. The evaluation results are shown in Table 1. ◦: a case where there is no change (warpage) in appearance after heating x: a case where appearance change (warpage) occurs after heating

(319) TABLE-US-00001 TABLE 1 Reference Reference Reference Reference Reference Reference Reference Reference Example 1-1 Example 1-2 Example 1-3 Example 1-4 Example 2-1 Example

2-2 Example 2-3 Example 2-4 Overlay layer PC PVC PET PC PC PVC PET PC Second adhesive layer Thermosetting resin (epoxy-based resin) None Intermediate layer PC PVC PET Vinyl chloride PC PVC PET Vinyl chloride First adhesive layer Thermosetting resin (epoxy-based resin) None Base material PC PVC PET PC PC PVC PET PC Adhesion ○ ○ ○ ○ ⊙ ⊙ ⊙ ⊙ Environmental ○ X ○ X ○ X ○ X consideration Durability* ○ ○ ○ X ○ ○ ○ X *Change in appearance after heating (warpage)

(320) The following can be seen from Table 1.

(321) When the base material and the intermediate layer, and the intermediate layer and the overlay layer are respectively bonded by a thermosetting resin or fusion, good adhesion can be obtained.

(322) From the viewpoint of improving adhesion, it is preferable to bond the base material and the intermediate layer and bond the intermediate layer and the overlay layer by fusion.

(323) From the viewpoint of environmental consideration, it is preferable to use a PC film or a PET film as the base material, the intermediate layer, and the overlay layer.

(324) From the viewpoint of improving durability, it is preferable to use a PC film or a PVC film as the base material, the intermediate layer, and the overlay layer.

(325) From the viewpoint of improving environmental consideration and durability, it is preferable to use a PC film as the base material, the intermediate layer, and the overlay layer.

Examples 1 to 3

(326) First, the layers shown in Table 2 were laminated to thereby prepare a recording medium having the layer configuration illustrated in FIG. 15. Next, a 100 μm-thick PET film having a frame shape (see FIG. 16) was prepared as an intermediate layer, and a recording medium was fitted in the frame of the PET film. The thickness of the recording medium and the PET film was set to be substantially the same. Next, a laminate was obtained in a similar manner to Reference Example 2-1 except that the intermediate layer in which the recording medium was fitted as described above was used. Note that the interface of the recording medium is also bonded by a heating and pressurizing process after the base material, the intermediate layer, and the overlay layer are laminated.

Example 4

(327) A laminate was obtained in a similar manner to Example 1 except that a recording medium having the layer configuration illustrated in FIG. 24 was prepared by laminating the layers shown in Table 3.

Example 5

(328) A laminate was obtained in a similar manner to Example 1 except that a recording medium having the layer configuration illustrated in FIG. 19 was prepared by laminating the layers shown in Table 3.

Example 6

(329) A laminate was obtained in a similar manner to Example 1 except that a recording medium having the layer configuration illustrated in FIG. 20 was prepared by laminating the layers shown in Table 3.

Example 7

(330) A laminate was obtained in a similar manner to Example 1 except that a recording medium having the layer configuration illustrated in FIG. 21 was prepared by laminating the layers shown in Table 4.

Example 8

(331) A laminate was obtained in a similar manner to Example 1 except that a recording medium having the layer configuration illustrated in FIG. 22 was prepared by laminating the layers shown in Table 4.

Example 9

(332) A laminate was obtained in a similar manner to Example 1 except that a recording medium having the layer configuration illustrated in FIG. 21 was prepared by laminating the layers shown

layer (1) Base material PET PC PC Base material PC PC Adhesion Average peel strength 0.3 0.3 7.0 [N/cm] Evaluation result X X ○ Interface with lowest Interface between (6) Interface between (6) Interface between UV average peel strength color development layer color development layer cut layer and OCA in and (7) heat insulating and (7) heat insulating (12) protective layer layer layer Forgery preventing Evaluation result ○ ○ ○ property Color developability Evaluation result ○ ○ X Color gamut Evaluation result ○ ○ ○

(343) TABLE-US-00003 TABLE 3 Example 2 Example 4 Example 5 Example 6 Overlay layer PC PC PC PC Recording medium (12) Protective layer PC PC PC PC OCA OCA OCA OCA UV cut layer UV cut layer UV cut layer UV cut layer UV resin UV resin UV resin UV resin (11) Pressure-sensitive OCA OCA OCA DCA sensitive adhesive layer (10) Heat insulating UV resin UV resin UV resin UV resin layer Matrix polymer OCA layer (9) Color Color Color Color Color development layer development development development development layer Y1 layer Y1 layer Y1 layer Y1 (8) Pressure-sensitive OCA OCA OCA OCA adhesive layer (7) Heat insulating UV resin None UV resin UV resin layer Matrix polymer OCA layer (6) Color Color Color Color Color development layer development development development development layer C1 layer C1 layer C1 layer 1 (5) Pressure-sensitive OCA OCA OCA OCA adhesive layer (4) Heat insulating UV resin None UV resin UV resin layer Matrix polymer OCA layer (3) Color Color Color Color Color development layer development development development development layer M1 layer M1 layer M1 layer M1 (2) Pressure-sensitive OCA None None None adhesive layer (1) Base material PC None None None Base material PC PC PC PC Adhesion Average peel strength 0.3 6.5 5.0 7.0 [N/cm] Evaluation result X ○ ○ ○ Interface with lowest Interface between Interface between Interface between Interface between average peel strength (6) color UV cut layer and UV cut layer and UV cut layer and development OCA in (12) OCA in (12) OCA in (12) layer and (7) heat protective layer protective layer protective layer insulating layer Forgery preventing Evaluation result ○ ○ ○ ○ property Color developability Evaluation result ○ ○ X ○ Color gamut Evaluation result ○ X ○ ○ ○

(344) TABLE-US-00004 TABLE 4 Example 2 Example 7 Example 8 Example 9 Example 10 Overlay layer PC PC PC PC PET Recording (12) Protective PC PC PC PC PET medium layer OCA OCA OCA OCA OCA UV cut layer UV cut layer UV cut layer UV cut layer UV cut layer UV resin UV resin UV resin UV resin UV resin (11) Pressure-sensitive OCA OCA OCA OCA OCA sensitive adhesive layer (10) Heat UV resin None None None None insulating layer (9) Color Color Color Color Color Color development development development development development development layer layer Y1 layer Y1 layer Y1 layer Y1 layer Y1 (8) Pressure-sensitive OCA None None None None sensitive adhesive layer (7) Heat UV resin PC PC Easy adhesion- Easy adhesion-insulating layer Matrix polymer treated PET treated PET layer (6) Color Color Color Color Color Color development development development development development development layer layer C1 layer C1 layer C1 layer C1 layer C1 (5) Pressure-sensitive OCA None None None OCA sensitive adhesive layer (4) Heat UV resin PC PC PC UV resin insulating layer OCA (3) Color Color Color Color Color Color development development development development development development development layer layer M1 layer M1 layer M1 layer M1 layer M1 (2) Pressure-sensitive OCA None None None None sensitive adhesive layer (1) Base PC None None None Easy adhesion- material treated PET Base material PC PC PC PC PET Adhesion Average peel 0.3 1.0 6.0 7.0 7.0 strength [N/cm] Evaluation result X X ○ ○ ○ Interface with Interface Interface Interface Interface Interface lowest average between between between between between between peel strength (6) color (6) color UV cut layer UV cut layer UV cut layer development development and OCA layer and OCA layer and OCA layer layer and (7) layer and (7) in (12) in (12) in (12) heat insulating heat insulating protective protective protective layer layer layer Forgery Evaluation result ○ ○ ○ ○ ○ preventing property Color Evaluation result ○ ○ ○ ○ ○ developability Color gamut Evaluation result ○ ○ ○ ○ ○

(345) Details of each member described in Tables 2, 3, and 4 are as follows. PC: PC film PET: PET

film Easy adhesion-treated PET: PET film subjected to easy adhesion treatment (DIAFOIL (registered trademark) manufactured by Mitsubishi Chemical Corporation) OCA: optical clear adhesive UV resin: ultraviolet curable resin layer (acrylic resin layer for hard coat) Matrix polymer layer: resin layer (specifically, polycarbonate-based resin layer) containing the same type of polymer as matrix polymer contained in adjacent color development layer Color development layer Y1: color development layer containing: leuco dye that develops yellow color; developer; and polycarbonate-based resin, in which the content of the polycarbonate-based resin in the color development layer is 58 mass % Color development layer Y2: color development layer containing: leuco dye that develops yellow color; developer; and polycarbonate-based resin, in which the content of the polycarbonate-based resin in the color development layer is 58 mass % Color development layer C1: color development layer containing: leuco dye that develops cyan color; developer; and polycarbonate-based resin, in which the content of the polycarbonate-based resin in the color development layer is 65 mass % Color development layer C2: color development layer containing: leuco dye that develops cyan color; developer; and polycarbonate-based resin, in which the content of the polycarbonate-based resin in the color development layer is 65 mass % Color development layer M1: color development layer containing: leuco dye that develops magenta color; developer; and polycarbonate-based resin, in which the content of the polycarbonate-based resin in the color development layer is 58 mass % Color development layer M2: color development layer containing: leuco dye that develops magenta color; developer; and polycarbonate-based resin, in which the content of the polycarbonate-based resin in the color development layer is 58 mass % (346) The following can be seen from Tables 2, 3, and 4.

(347) When the intermediate layer between the color development layers includes the matrix polymer layer, the ultraviolet curable resin layer, and the pressure-sensitive adhesive layer, adhesion between the color development layer and the intermediate layer can be improved (see, the evaluation results of Example 5).

(348) When the intermediate layer between the color development layers includes the pressure-sensitive adhesive layer, the ultraviolet curable resin layer, and the pressure-sensitive adhesive layer, the adhesion between the color development layer and the intermediate layer can be improved (see, the evaluation results of Examples 6 and 10).

(349) When the intermediate layer between the color development layers includes the matrix polymer layer and the film, the adhesion between the color development layer and the intermediate layer can be improved (see, the evaluation results of Example 8).

(350) When the intermediate layer between the color development layers includes the easily adhesion-treated film, the adhesion between the color development layer and the intermediate layer can be improved (see, the evaluation results of Examples 9 and 10).

Reference Examples 3-1 to 3-8

(351) A PC film having a thickness of 25 μm , a polycarbonate-based resin-containing layer having a thickness of 5 μm , and a PC film having a thickness of 25 μm were laminated, and then the laminate was heated and pressurized at a temperature of 180° C. to be fused, thereby obtaining a sample. As the polycarbonate-based resin-containing layer, a layer having the composition shown in Table 5 was used.

(352) (Adhesion)

(353) First, the average peel strength between the layers of the sample was measured. The average peel strength was measured by the method for measuring the average peel strength of the laminate described in the first embodiment. Next, the measured average peel strength was evaluated according to the following criteria. ◦: The average peel strengths between the layers are all 3.5 N/cm or more. x: At least one of the average peel strengths between the layers is less than 3.5 N/cm.

(354) The evaluation results are shown in Table 5 and FIG. 26. Note that the average peel strength shown in Table 5 represents the average peel strength between the polycarbonate-based resin-

containing layer and the PC film.

(355) TABLE-US-00005 TABLE 5 Reference Reference Reference Reference Reference Reference
Reference Reference Example 3-1 Example 3-2 Example 3-3 Example 3-4 Example 3-5 Example
3-6 Example 3-7 Example 3-8 Layer configuration of sample PC film (thickness: 25 μm) PC-based
resin-containing layer (thickness: 5 μm) PC film (thickness: 25 μm) Composition of Matrix 100 92
84 82 80 78 76 67 PC-based resin- polymer containing layer [mass %] Developer 0 8 16 18 20 22
24 33 [mass %] Adhesion Average peel 9.0 9.0 9.0 2.7 2.1 1.6 1.4 0.7 strength [N/cm] Evaluation
○ ○ ○ X X X X X result

(356) Details of each member and each material described in Table 5 are as follows. OCA: optical
clear adhesive Ultraviolet curable resin layer: acrylic resin layer for hard coat Matrix polymer:
polycarbonate-based resin Developer: compound represented by Formula (3)

(357) Table 5 and FIG. 26 show that when the proportion of the developer in the total amount of
the developer and the matrix polymer is 16 mass % or less, the peel strength can be 3.5 N/cm or
more.

REFERENCE SIGNS LIST

(358) 10, 10A, 40, 40A Laminate 11, 21, 51 Base material 12, 14 Adhesive layer 13, 16
Intermediate layer 13A, 16A Accommodation part 15 Overlay layer 20, 20A, 20B, 20C, 20D, 20E,
20F, 20G, 20H, 50 Recording medium 22, 25, 28, 33 Pressure-sensitive adhesive layer 23, 26, 29,
34, 26A, 29A, 34A, 26B, 29B, 34B Heat insulating layer 24, 27, 30, 52 Color development layer
26A1, 29A1, 34A1 Resin layer 26A2, 29A2, 34A2, 26B2, 29B2, 34B2 Ultraviolet curable resin
layer 26B1, 29B1, 34B1 Pressure-sensitive adhesive layer 31, 36 Protective layer 32A, 32B, 32C,
35A, 35B, 35C, 37A, 37B, 37C, 38A, 38B, 38C Intermediate layer 36A Ultraviolet curable resin
layer 36B UV cut layer 36C Pressure-sensitive adhesive layer 36D Base material 52C, 52M, 52Y
Microcapsule 60 Test piece 60A, 60B Adherend 61 Tension member 62 Clamp apparatus 71 Test
stand 72 Jig 73A, 73B Movable roll 100 Smartphone 200 Notebook personal computer 300
Decorative container 400 Booklet

Claims

1. A laminate comprising: a base material; a first intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the first intermediate layer, wherein the accommodation part is provided in a part of a plane of the first intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the first intermediate layer or a recess recessed in a thickness direction of the first intermediate layer, the recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin, the base material, the first intermediate layer, and the overlay layer contain a resin material including a polycarbonate-based resin, and the base material and the first intermediate layer are bonded to each other by fusion, and the first intermediate layer and the overlay layer are bonded to each other by fusion.
2. The laminate according to claim 1, wherein the resin material further includes a polyethylene terephthalate-based resin.
3. The laminate according to claim 1, wherein the color development layer is configured to be capable of changing a colored state by laser light, and a change in the colored state is an irreversible change.
4. The laminate according to claim 1, wherein the color development layer further contains a photothermal conversion material.
5. The laminate according to claim 1, wherein the recording medium includes a plurality of the color development layers, and the plurality of color development layers contains coloring

compounds developing colors of different hues from one another.

6. The laminate according to claim 1, wherein the recording medium includes a plurality of the color development layers and a plurality of second intermediate layers, and each of the plurality of second intermediate layers is provided between the color development layers adjacent to each other.

7. The laminate according to claim 6, wherein at least one of the plurality of second intermediate layers includes an ultraviolet curable resin layer and a pressure-sensitive adhesive layer.

8. The laminate according to claim 6, wherein at least one of the plurality of second intermediate layers includes a resin layer, an ultraviolet curable resin layer, and a pressure-sensitive adhesive layer, the ultraviolet curable resin layer is provided between the resin layer and the pressure-sensitive adhesive layer, and the resin layer contains a resin material of a same material as the matrix resin.

9. The laminate according to claim 6, wherein at least one of the plurality of second intermediate layers includes a first pressure-sensitive adhesive layer, an ultraviolet curable resin layer, and a second pressure-sensitive adhesive layer in order.

10. The laminate according to claim 6, wherein at least one of the plurality of second intermediate layers is a film subjected to easy an adhesion treatment.

11. The laminate according to claim 1, wherein the recording medium includes a plurality of the color development layers, a plurality of second intermediate layers, and a protective layer, the plurality of color development layers includes a first color development layer, a second color development layer, and a third color development layer, the first color development layer, a first layer of the plurality of second intermediate layers, the second color development layer, a second layer of the plurality of second intermediate layers, the third color development layer, a third layer of the plurality of second intermediate layers, and the protective layer are laminated in this order, and the first color development layer, the second color development layer, and the third color development layer contain coloring compounds developing colors of different hues from one another.

12. The laminate according to claim 1, wherein a proportion of the developer in a total amount of the developer and the matrix resin is 16 mass % or less.

13. A card comprising the laminate according to claim 1.

14. A housing comprising the laminate according to claim 1.

15. A laminate comprising: a base material; a first intermediate layer provided on the base material and having an accommodation part; a recording medium provided in the accommodation part; and an overlay layer provided on the first intermediate layer, wherein the accommodation part is provided in a part of a plane of the first intermediate layer, the accommodation part is a through hole penetrating in a thickness direction of the first intermediate layer or a recess recessed in a thickness direction of the first intermediate layer, the recording medium includes a color development layer containing: a coloring compound having an electron donating property; a developer having an electron accepting property; and a matrix resin, the base material, the first intermediate layer, and the overlay layer contain a resin material including a polycarbonate-based resin, and the base material and the first intermediate layer are bonded to each other by a thermal adhesive, and the first intermediate layer and the overlay layer are bonded to each other by a thermal adhesive.

16. The laminate according to claim 15, wherein the thermal adhesive contains a thermosetting resin.
