



US012397855B1

(12) **United States Patent**  
**Kariya**

(10) **Patent No.:** **US 12,397,855 B1**

(45) **Date of Patent:** **Aug. 26, 2025**

(54) **STEERING KNUCKLE CASTING AND  
STEERING KNUCKLE**

(71) Applicant: **HONDA FOUNDRY CO., LTD.,**  
Kawagoe (JP)

(72) Inventor: **Tomoichiro Kariya**, Kawagoe (JP)

(73) Assignee: **Honda Foundry Co., Ltd.**, Saitama  
(JP)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 0 days.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,799,811 B1 \* 10/2004 Dauber ..... B62D 7/18  
301/124.1  
11,021,187 B2 \* 6/2021 Johnson ..... B22D 25/02  
11,745,795 B2 \* 9/2023 Foti ..... B62D 7/16  
403/135  
11,780,495 B2 \* 10/2023 Reddehase ..... B62D 7/18  
280/93.512  
12,116,068 B2 \* 10/2024 Gruber ..... B60B 27/0052  
2019/0003022 A1 \* 1/2019 Cakrawala ..... B22C 9/22  
(Continued)

FOREIGN PATENT DOCUMENTS

CN 202783360 U 3/2013  
CN 204197009 U 3/2015  
(Continued)

*Primary Examiner* — Toan C To

(74) *Attorney, Agent, or Firm* — Carrier, Shende &  
Associates P.C.; Fulchand P. Shende; Joseph P. Carrier

(21) Appl. No.: **18/703,826**

(22) PCT Filed: **Jun. 1, 2022**

(86) PCT No.: **PCT/JP2022/022277**

§ 371 (c)(1),

(2) Date: **Mar. 3, 2025**

(87) PCT Pub. No.: **WO2023/105819**

PCT Pub. Date: **Jun. 15, 2023**

(30) **Foreign Application Priority Data**

Dec. 10, 2021 (JP) ..... 2021-200582

(51) **Int. Cl.**

**B62D 7/18** (2006.01)

**B22D 25/02** (2006.01)

(52) **U.S. Cl.**

CPC ..... **B62D 7/18** (2013.01); **B22D 25/02**  
(2013.01)


(58) **Field of Classification Search**

CPC ..... B62D 7/18; B22D 25/02  
See application file for complete search history.

(57) **ABSTRACT**

A steering knuckle casting **20** includes a plan portion **22** and a product portion **23** formed along a flow of molten metal **21**. The product portion **23** includes an intermediate portion **26**, a first fastening portion **27** integrally formed at one end of the intermediate portion **26**, a second fastening portion **28** integrally formed at the other end of the intermediate portion **26**, and a first rib **31** and a second rib **32** integrally formed in the intermediate portion **26** to extend from the first fastening portion **27** to the second fastening portion **28**. The first rib **31** and the second rib **32** are not parallel to each other, and are disposed in a V shape such that a rib spacing **W1** on a first fastening portion **27** side is narrower than a rib spacing **W2** on a second fastening portion **28** side.

**5 Claims, 10 Drawing Sheets**



(56)

**References Cited**

U.S. PATENT DOCUMENTS


2020/0047794 A1 \* 2/2020 Fleury ..... B29C 43/003  
2020/0223272 A1 7/2020 Hosoi


FOREIGN PATENT DOCUMENTS

JP 2006-007802 A 1/2006  
JP 2017-074863 A 4/2017  
JP 2020-111173 A 7/2020  
KR 2018-0110333 A 10/2018

\* cited by examiner

**FIG.1**



**FIG.2**



**FIG.3**


FIG. 4





EMBODIMENT:



**FIG. 5**

COMPARATIVE EXAMPLE:
















FIG.8






**FIG. 9a**  
(CONVENTIONAL TECHNIQUE)



**FIG. 9b**  
(CONVENTIONAL TECHNIQUE)

**FIG.10**  
(CONVENTIONAL  
TECHNIQUE)



1

# STEERING KNUCKLE CASTING AND STEERING KNUCKLE

## TECHNICAL FIELD

The present invention relates to a steering knuckle casting and a steering knuckle. In the invention, the steering knuckle as a product (product steering knuckle) is simply referred to as a “steering knuckle”, and is distinguished from a steering knuckle casting.

## BACKGROUND ART

A member referred to as a steering knuckle that holds a wheel is attached to a vehicle such as a passenger car.

Such a steering knuckle including a reinforcing rib is known (for example, refer to Patent Document 1 (FIG. 2)).

Patent Document 1 will be described based on the following drawing.

FIG. 9 is a front view and a right side view of a conventional steering knuckle.

As shown in FIG. 9(a), a steering knuckle **100** includes, as basic elements, an intermediate portion **101**; a first connecting portion **102** formed at one end of the intermediate portion **101**; and a second connecting portion **103** formed at the other end of the intermediate portion **101**.

Fastened members such as a lower arm, an upper arm, a brake carrier, and a link member are fastened to the first connecting portion **102** and the second connecting portion **103** using bolts (Patent Document 1, paragraph 0013).

As shown in FIG. 9(b), the steering knuckle **100** is provided with a first rib **104** and a second rib **105**.

As shown in FIG. 9(a), when a line passing through the center of the first connecting portion **102** and the center of the second connecting portion **103** is referred to as a center line **106**, the first rib **104** and the second rib **105** are provided to be parallel to the center line **106**.

A steering knuckle **200** having a form different from that in Patent Document 1 will be described based on FIG. 10.

As shown in FIG. 10, the conventional steering knuckle **200** includes a product intermediate portion **201**; an axle fastening portion **202** integrally formed at one end of the product intermediate portion **201**; a damper fastening portion **203** integrally formed at the other end of the product intermediate portion **201**; a rod fastening portion **204** formed to project from the axle fastening portion **202** toward the right in the drawing; a brake fastening portion **205** formed to project from the axle fastening portion **202** toward the left in the drawing; and a lower arm fastening portion **206** formed to project from the axle fastening portion **202** toward the bottom in the drawing.

An axle is fastened to the axle fastening portion **202**.

A damper is fastened to the damper fastening portion **203**.

A steering tie rod is fastened to the rod fastening portion **204**.

A brake carrier (brake caliper) is fastened to the brake fastening portion **205**.

A lower arm is fastened to the lower arm fastening portion **206**.

The present inventors attached ribs (a pair of reinforcing ribs parallel to each other), which are similar to those in Patent Document 1, to the steering knuckle **200**.

Namely, a first reinforcing rib **207** and a second reinforcing rib **208** extending from the axle fastening portion **202** to the damper fastening portion **203** were integrally formed in the product intermediate portion **201**.

2

The rigidity is improved by the first reinforcing rib **207** and the second reinforcing rib **208**.

On the other hand, it was found that the castability (running of metal and solidification directionality) was sacrificed due to the first reinforcing rib **207** and the second reinforcing rib **208** being provided. The reason for this will be described in detail in a “comparative example” to be described later.

## CITATION LIST

### Patent Document

Patent Document 1: Japanese Unexamined Patent Publication No. 2017-74863

## SUMMARY OF THE INVENTION

### Problem to be Solved by the Invention

An object of the invention is to provide a technique of improving castability despite the fact that a first reinforcing rib and a second reinforcing rib are provided in a steering knuckle casting for the purpose of improving rigidity.

### Means for Solving Problem

According to a first aspect of the invention, there is provided a steering knuckle casting from which a steering knuckle as a product is obtained by performing machining on the steering knuckle casting. The steering knuckle casting is a casting product including a plan portion and a product portion formed along a flow of molten metal, designed such that the product portion solidifies and then the plan portion solidifies, and obtained by separating the plan portion from the product portion after the solidification, sending the plan portion back to a remelting process, and performing the machining on the product portion. The product portion includes an intermediate portion, a first fastening portion integrally formed at one end of the intermediate portion and formed on a plan portion side, a second fastening portion integrally formed at the other end of the intermediate portion, and a first rib and a second rib integrally formed in the intermediate portion to extend from the first fastening portion to the second fastening portion. The first rib and the second rib are not parallel to each other, and are disposed in a V shape such that a rib spacing on a first fastening portion side is narrower than a rib spacing on a second fastening portion side.

According to a second aspect of the invention, preferably, in the steering knuckle casting according to the first aspect, the plan portion includes a final solidification portion that is most delayed in the solidification, and an intersection point between a longitudinal axis of the first rib and a longitudinal axis of the second rib overlaps the final solidification portion.

According to a third aspect of the invention, preferably, in the steering knuckle casting according to the first or second aspect, the first fastening portion is a portion to which an axle is fastened, and the second fastening portion is a portion to which a damper is fastened.

According to a fourth aspect of the invention, there is a steering knuckle including: a product intermediate portion; an axle fastening portion which is integrally formed at one end of the product intermediate portion, and to which an axle is fastened; a damper fastening portion which is integrally formed at the other end of the product intermediate portion,

3

and to which a damper is fastened; and a first reinforcing rib and a second reinforcing rib integrally formed in the product intermediate portion to extend from the axle fastening portion to the damper fastening portion. The first reinforcing rib and the second reinforcing rib are not parallel to each other, and are disposed in a V shape such that a rib spacing on an axle fastening portion side is narrower than a rib spacing on a damper fastening portion side.

#### Effect of the Invention

In the first aspect of the invention, the first rib and the second rib are disposed in a V shape such that the first rib and the second rib are directed toward the plan portion.

After the filling of the molten metal is completed in a casting process, heat is removed by a mold, and the solidification of the molten metal starts. At this time, the unsolidified molten metal moves toward the plan portion through the first rib and the second rib. According to the invention, since the first rib and the second rib are directed toward the plan portion, the unsolidified molten metal smoothly moves toward the plan portion. As a result, solidification directionality is significantly improved. Since the solidification directionality is improved, castability is improved.

Namely, according to the invention, a technique of improving the castability despite the fact that the first rib and the second rib are provided in the steering knuckle casting for the purpose of improving rigidity is provided.

In the second aspect of the invention, the intersection point between the longitudinal axis of the first rib and the longitudinal axis of the second rib overlaps the final solidification portion in the plan portion.

Since the unsolidified molten metal moves directly toward the final solidification portion, solidification directionality is further improved.

In the third aspect of the invention, the first rib and the second rib span between the portion to which the axle is fastened and the portion to which the damper is fastened.

Large bending due to an external force is applied between the portion to which the axle is fastened and the portion to which the damper is fastened. The first rib and the second rib are provided at such a portion to sufficiently increase the rigidity. Namely, sufficient rigidity can be given without increasing the thickness of the intermediate portion. As a result, a reduction in the thickness and weight of the steering knuckle can be easily achieved.

In the fourth aspect of the invention, the first reinforcing rib and the second reinforcing rib are disposed in a V shape in the steering knuckle.

Similarly to the first aspect, since the first reinforcing rib and the second reinforcing rib are directed toward the plan portion, the unsolidified molten metal smoothly moves toward the plan portion. As a result, solidification directionality is significantly improved. Since the solidification directionality is improved, castability is improved.

Namely, according to the invention, a technique of improving the castability despite the fact that the first reinforcing rib and the second reinforcing rib are provided in the steering knuckle for the purpose of improving rigidity is provided.

#### BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a plan view of a steering knuckle according to the invention;

FIG. 2 is a view from arrow 2 in FIG. 1 (a front view of the steering knuckle);

4

FIG. 3 is a view from arrow 3 in FIG. 1 (a right side view of the steering knuckle);

FIG. 4 is a plan view of a steering knuckle casting according to the invention;

FIG. 5 is a plan view of a steering knuckle casting according to a comparative example;

FIGS. 6(a) to 6(d) are views describing the solidification time of a first reinforcing rib;

FIGS. 7(a) to 7(d) are views describing the solidification time of a second reinforcing rib;

FIG. 8 is a view describing a more preferred embodiment;

FIG. 9(a) is a front view of a conventional steering knuckle, and FIG. 9(b) is a right side view of the conventional steering knuckle; and

FIG. 10 is a perspective view of another conventional steering knuckle.

#### MODE(S) FOR CARRYING OUT THE INVENTION

An embodiment of the invention will be described below based on the accompanying drawings.

#### EMBODIMENT

A steering knuckle 10 as a product is shown in FIG. 1 to FIG. 3. The steering knuckle 10 is obtained by performing machining or the like on a steering knuckle casting.

As shown in FIG. 1, the steering knuckle 10 includes a product intermediate portion 11; an axle fastening portion 12 integrally formed at one end of the product intermediate portion 11; a damper fastening portion 13 integrally formed at the other end of the product intermediate portion 11; a rod fastening portion 14 formed to project from the axle fastening portion 12 toward the right in the drawing; and a brake fastening portion 15 formed to project from the axle fastening portion 12 toward the left in the drawing.

An axle is fastened to the axle fastening portion 12.

A machining hole 19 is formed in the damper fastening portion 13, and a damper is fastened to the machining hole 19.

A steering tie rod is fastened to the rod fastening portion 14.

A brake caliper is fastened to the brake fastening portion 15.

A first reinforcing rib 16 and a second reinforcing rib 17 are integrally formed in the product intermediate portion 11 to extend from the axle fastening portion 12 to the damper fastening portion 13. The first reinforcing rib 16 and the second reinforcing rib 17 are disposed non-parallel to each other, and are disposed in a V shape such that a rib spacing on an axle fastening portion side 12 is narrower than a rib spacing on a damper fastening portion side 13.

As shown in FIG. 2, the steering knuckle 10 integrally includes an arm fastening portion 18 at a lower portion thereof. A lower arm is fastened to the arm fastening portion 18. For other portions, the reference letters or numerals in FIG. 1 are used, and detailed description thereof will be omitted.

As shown in FIG. 3, the first reinforcing rib 16 and the second reinforcing rib 17 are integrally formed in the product intermediate portion 11 to extend from the axle fastening portion 12 to the damper fastening portion 13. For other portions, the reference letters or numerals in FIG. 1 are used, and detailed description thereof will be omitted.

## 5

A steering knuckle casting serving as an origin for the steering knuckle **10** described above will be described below.

As shown in FIG. 4, a steering knuckle casting **20** includes a plan portion **22** and a product portion **23** formed along the flow of molten metal **21**. The product portion **23** solidifies, and then the plan portion **22** solidifies. The vicinity of a central portion of the plan portion **22** is a final solidification portion **29**.

When solidification is completed, the plan portion **22** is separated from the product portion **23** along a separation line **24**.

The plan portion **22** is sent back to a remelting process, and the product portion **23** is machined to obtain the steering knuckle **10** described in FIG. 1 to FIG. 3.

The product portion **23** includes an intermediate portion **26**; a first fastening portion **27** integrally formed at one end (plan portion **22** side) of the intermediate portion **26**; a second fastening portion **28** integrally formed at the other end of the intermediate portion **26**; and a first rib **31** and a second rib **32** that are integrally formed in the intermediate portion **26** to extend from the first fastening portion **27** to the second fastening portion **28**.

The first fastening portion **27** corresponds to a portion to which the axle is fastened (axle fastening portion **12** in FIG. 1), and the second fastening portion **28** corresponds to a portion to which the damper is fastened (damper fastening portion **13** in FIG. 1).

The product portion **23** further integrally includes a projecting portion **33** projecting from the intermediate portion **26** toward the right in the drawing. The rod fastening portion (reference numeral **14** in FIG. 1) is formed in the projecting portion **33**, which projects, in a post-process.

A center line **34** is a line passing through the center of the first fastening portion **27** and the center of the second fastening portion **28**.

The first rib **31** and the second rib **32** are not parallel to the center line **34**, and are disposed in a V shape such that a rib spacing **W1** on a first fastening portion **27** side is narrower than a rib spacing **W2** on a second fastening portion **28** side.

Incidentally, in the embodiment, both the first rib **31** and the second rib **32** are made non-parallel to the center line **34**; however, only one may be made non-parallel to the center line **34**, and the other may be made parallel (including substantially parallel) to the center line **34**. In short, the first rib **31** and the second rib **32** may be disposed in a V shape.

In order to examine the superiority of the first rib **31** and second rib **32** of the invention disposed in a V shape, a steering knuckle casting in which a pair of ribs are disposed parallel to each other is taken as a "comparative example".

As shown in FIG. 5, a steering knuckle casting **120** in the comparative example includes a plan portion **122** and a product portion **123**.

The product portion **123** includes an intermediate portion **126**; a first fastening portion **127**; a second fastening portion **128**; a first rib **131** and a second rib **132** that are integrally formed in the intermediate portion **126** to extend from the first fastening portion **127** to the second fastening portion **128**; and a projecting portion **133**.

The first rib **131** and the second rib **132** are parallel to a center line **134** passing through the center of the first fastening portion **127** and the center of the second fastening portion **128**.

The steering knuckle casting **20** (embodiment) and the steering knuckle casting **120** (comparative example)

## 6

described above will be compared to each other. This comparison will be described based on FIG. 6 and FIG. 7.

FIG. 6 is a view describing the solidification status of the first reinforcing rib.

FIG. 6(a) shows the steering knuckle casting **120** (comparative example), and FIG. 6(b) is a view describing solidification times in a cross section taken along line b-b of FIG. 6(a).

In FIG. 6(b), a solidification time **t1** in areas with diagonal lines is 10 to 18 seconds. A solidification time **t2** in areas with countless dots is 18 to 22 seconds.

Namely, in the intermediate portion including the first rib **131**, solidification progresses (is directed) from left and right surface layers toward the center. A distance between the left area with the solidification time **t2** and the right area with the solidification time **t2** is denoted by **D1**.

FIG. 6(c) shows the steering knuckle casting **20** (embodiment), and FIG. 6(d) is a view describing solidification times in a cross section taken along line d-d of FIG. 6(c).

In FIG. 6(d), the solidification time **t1** in areas with diagonal lines is 10 to 18 seconds. The solidification time **t2** in areas with countless dots is 18 to 22 seconds.

Namely, in the intermediate portion including the first rib **31**, solidification progresses (is directed) from left and right surface layers toward the center. A distance between the left area with the solidification time **t2** and the right area with the solidification time **t2** is denoted by **D2**.

The distance **D2** is much smaller than the distance **D1**. In addition, in FIG. 6(d), the tips of the areas with the solidification time **t2** form a V shape, and the division of the solidification direction is clear. On the other hand, in FIG. 6(b), the division of the solidification direction is not clear.

In FIG. 6(d), since the division of the solidification direction is clear, the unsolidified molten metal is pushed out to the first fastening portion **27** and the second fastening portion **28**. As a result, a casting defect such as a cavity is less likely to remain in the first rib **31**.

On the other hand, in FIG. 6(b), since the division of the solidification direction is not clear, a casting defect such as a cavity is likely to remain.

The above-described tendency will also be verified in FIG. 4.

In FIG. 4, after the filling of the molten metal **21** is completed in a casting process, heat is removed (cooled) by a mold, and the solidification of the molten metal **21** starts. The solidification of the molten metal **21** may be partially uneven depending on the shape of the product or the shape of the mold. In a final solidification portion, generally, a shrinkage cavity is likely to occur due to solidification shrinkage of the metal.

As described in FIG. 6(d), the unsolidified molten metal moves toward the first fastening portion **27** and the second fastening portion **28**.

In FIG. 4, the molten metal moving toward the first fastening portion **27** moves toward the final solidification portion **29**, and the molten metal moving toward the second fastening portion **28** moves toward the center of the second fastening portion **28**. The center of the second fastening portion **28** becomes a delayed solidification portion **30** on a product side.

A shrinkage cavity is likely to occur in the final solidification portion **29** and the delayed solidification portion **30** on the product side. Since the solidification directionality is clear, portions where a shrinkage cavity occurs are limited to the final solidification portion **29** and the delayed solidification portion **30** on the product side.

Since the final solidification portion **29** is included in the plan portion **22** partitioned by a parting line **24**, the final solidification portion **29** does not affect the product portion **23**.

In addition, the delayed solidification portion **30** on the product side is removed when the machining hole (reference numeral **19** in FIG. **1**) is machined.

Namely, solidification starts from the intermediate portion **26**. As a result, by controlling the solidification directionality, a casting defect such as a shrinkage cavity is prevented from occurring in the product portion **23** including the intermediate portion **26**, and as a result, the internal quality is improved, the strength is secured, the productivity is improved, and the castability is improved.

On the other hand, since the division of the solidification direction is not clear in the comparative example described in FIG. **6(a)** and FIG. **6(b)**, the risk of a shrinkage cavity also occurring in the product portion remains compared to the embodiment described in FIG. **6(c)** and FIG. **6(d)**.

FIG. **7** is a view describing the solidification status of the second reinforcing rib.

FIG. **7(a)** shows the steering knuckle casting **120** (comparative example), and FIG. **7(b)** is a view describing solidification times in a cross section taken along line b-b of FIG. **7(a)**.

In FIG. **7(b)**, the solidification time **t1** in areas with diagonal lines is 10 to 16 seconds. A solidification time **t3** in areas with countless dots is 16 to 18 seconds. A distance between the left area with the solidification time **t3** and the right area with the solidification time **t3** is denoted by **D3**.

Incidentally, since the second rib **132** is affected by the projecting portion **133** having a large heat capacity, the second rib **132** is much less likely to solidify than the first rib.

FIG. **7(c)** shows the steering knuckle casting **20** (embodiment), and FIG. **7(d)** is a view describing solidification times in a cross section taken along line d-d of FIG. **7(c)**.

In FIG. **7(d)**, the solidification time **t1** in areas with diagonal lines is 10 to 16 seconds. The solidification time **t3** in areas with countless dots is 16 to 18 seconds.

A distance between the left area with the solidification time **t3** and the right area with the solidification time **t3** is denoted by **D4**.

Incidentally, since the second rib **32** is affected by the projecting portion **33** having a large heat capacity, the second rib **32** is much less likely to solidify than the first rib.

The distance **D4** is much smaller than the distance **D3**. In addition, in FIG. **7(d)**, the tips of the areas with the solidification time **t3** form a V shape, and the division of the solidification direction is clear. On the other hand, in FIG. **7(b)**, the division of the solidification direction is not clear.

In FIG. **7(d)**, since the division of the solidification direction is clear, the unsolidified molten metal is pushed out to the first fastening portion **27** and the second fastening portion **28**. As a result, a casting defect such as a cavity is less likely to remain in the first rib **31**.

On the other hand, in FIG. **7(b)**, since the division of the solidification direction is not clear, a casting defect such as a cavity is likely to remain.

Namely, according to FIG. **7(c)** and FIG. **7(d)**, solidification starts from the intermediate portion. As a result, by controlling the solidification directionality, a casting defect such as a shrinkage cavity is prevented from occurring in the product portion including the intermediate portion, and as a result, the internal quality is improved, the strength is secured, and the productivity is improved.

On the other hand, since the division of the solidification direction is not clear in the comparative example described in FIG. **7(a)** and FIG. **7(b)**, the risk of a shrinkage cavity also occurring in the product portion remains compared to the embodiment described in FIG. **7(c)** and FIG. **7(d)**.

In FIG. **6** and FIG. **7**, there was a significant difference in solidification directionality between the comparative example and the embodiment. The reason for the occurrence of this difference will be estimated.

In FIG. **5** (comparative example), since the first rib **131** and the second rib **132** are parallel to each other, a longitudinal axis **131B** of the first rib **131** is not directed toward a final solidification portion **129** in the plan portion **122**. Similarly, a longitudinal axis **132B** of the second rib **132** is not directed toward the final solidification portion **129** in the plan portion **122**.

Some of the unsolidified molten metal moves toward the plan portion **122** along the longitudinal axes **131B** and **132B**, but does not move toward the final solidification portion **129**. For that reason, as shown in FIG. **6(b)** or FIG. **7(b)**, the division of the solidification direction is not clear.

On the other hand, in FIG. **4** (embodiment), the first rib **31** and the second rib **32** are disposed in a V shape, a longitudinal axis **31B** of the first rib **31** is directed toward the final solidification portion **29**, and a longitudinal axis **32B** of the second rib **32** is directed toward the final solidification portion **29**.

Some of the unsolidified molten metal moves toward the final solidification portion **29** along the longitudinal axes **31B** and **32B**. For that reason, as shown in FIG. **6(d)** or FIG. **7(d)**, the division of the solidification direction is clear.

Next, the preferred sizes of the rib spacings **W1** and **W2** shown in FIG. **4** were investigated.

Models 1 to 4 were created by setting the rib spacing **W1** to a ratio of "1.0" and setting the rib spacing **W2** to a ratio in a range of 1.15 to 1.45, and the castability of Models 1 to 4 was investigated.

In Model 1, the rib spacing **W1** was set to a ratio of 1.0, and the rib spacing **W2** was set to a ratio of 1.15.

In Model 2, the rib spacing **W1** was set to a ratio of 1.0, and the rib spacing **W2** was set to a ratio of 1.28.

In Model 3, the rib spacing **W1** was set to a ratio of 1.0, and the rib spacing **W2** was set to a ratio of 1.33.

In Model 4, the rib spacing **W1** was set to a ratio of 1.0, and the rib spacing **W2** was set to a ratio of 1.45.

In Model 1, **W2** was set to 1.15. Since the difference between **W1** and **W2** was small, the effect of a V shape was not exhibited, and an improvement in castability was small. The result is no good.

In Model 2, **W2** was set to 1.28. The effect of a V shape was sufficiently exhibited, and good castability was obtained. The result is good.

In Model 3, **W2** was set to 1.33. The effect of a V shape was sufficiently exhibited, and good castability was obtained. The result is good.

In Model 4, **W2** was set to 1.45. The angle formed by a V shape is increased, which affected the flowability of the metal. The result is somewhat no good.

As a result, when the rib spacing **W1** is set to a ratio of "1.0", it is recommended that the rib spacing **W2** is set to a ratio in a range of 1.28 to 1.33.

Next, a more preferred embodiment will be described.

As shown in FIG. **8**, the final solidification portion **29** is included in the plan portion **22**, and an intersection point between the longitudinal axis **31B** of the first rib **31** and the longitudinal axis **32B** of the second rib **32** overlaps the final solidification portion **29**. The intersection point does not



need to be the center of the final solidification portion **29**, and may be at an edge of the final solidification portion **29** as long as the intersection point is within the final solidification portion **29**.

Since the unsolidified molten metal moves toward the final solidification portion **29** along the longitudinal axes **31B** and **32B**, the solidification directionality becomes clearer, and the occurrence of a casting defect can be more reliably avoided.

Incidentally, in the embodiment, the axle is fastened to the first fastening portion **27**; however, an arm or a rod other than the axle may be fastened to the first fastening portion **27**.

Similarly, in the embodiment, the damper is fastened to the second fastening portion **28**; however, an arm or a rod other than the axle may be fastened to the second fastening portion **28**.

#### INDUSTRIAL APPLICABILITY

The invention is suitable for the steering knuckle that holds a wheel.

#### EXPLANATIONS OF LETTERS OR NUMERALS

**10** STEERING KNUCKLE  
**12** AXLE FASTENING PORTION  
**13** DAMPER FASTENING PORTION  
**16** FIRST REINFORCING RIB  
**17** SECOND REINFORCING RIB  
**20** STEERING KNUCKLE CASTING  
**21** MOLTEN METAL  
**22** PLAN PORTION  
**23** PRODUCT PORTION  
**24** SEPARATION LINE  
**26** INTERMEDIATE PORTION  
**27** FIRST FASTENING PORTION  
**28** SECOND FASTENING PORTION  
**29** FINAL SOLIDIFICATION PORTION  
**31** FIRST RIB  
**31B** LONGITUDINAL AXIS OF FIRST RIB  
**32** SECOND RIB  
**32B** LONGITUDINAL AXIS OF SECOND RIB  
**34** CENTER LINE  
**W1** RIB SPACING ON FIRST FASTENING PORTION SIDE  
**W2** RIB SPACING ON SECOND FASTENING PORTION SIDE

The invention claimed is:

1. A steering knuckle casting from which a steering knuckle as a product is obtained by performing machining on the steering knuckle casting, wherein the steering knuckle casting is a casting product including a plan portion and a product portion formed

along a flow of molten metal, designed such that the product portion solidifies and then the plan portion solidifies, and obtained by separating the plan portion from the product portion after the solidification, sending the plan portion back to a remelting process, and performing the machining on the product portion,

the product portion includes an intermediate portion, a first fastening portion integrally formed at one end of the intermediate portion and formed on a plan portion side, a second fastening portion integrally formed at the other end of the intermediate portion, and a first rib and a second rib integrally formed in the intermediate portion to extend from the first fastening portion to the second fastening portion, and

the first rib and the second rib are not parallel to each other, and are disposed in a V shape such that a rib spacing on a first fastening portion side is narrower than a rib spacing on a second fastening portion side.

2. The steering knuckle casting according to claim 1, wherein the plan portion includes a final solidification portion that is most delayed in the solidification, and an intersection point between a longitudinal axis of the first rib and a longitudinal axis of the second rib overlaps the final solidification portion.

3. The steering knuckle casting according to claim 2, wherein the first fastening portion is a portion to which an axle is fastened, and

the second fastening portion is a portion to which a damper is fastened.

4. The steering knuckle casting according to claim 1, wherein the first fastening portion is a portion to which an axle is fastened, and

the second fastening portion is a portion to which a damper is fastened.

5. A steering knuckle comprising:

a product intermediate portion;  
 an axle fastening portion which is integrally formed at one end of the product intermediate portion, and to which an axle is fastened;

a damper fastening portion which is integrally formed at the other end of the product intermediate portion, and to which a damper is fastened; and

a first reinforcing rib and a second reinforcing rib integrally formed in the product intermediate portion to extend from the axle fastening portion to the damper fastening portion,

wherein the first reinforcing rib and the second reinforcing rib are not parallel to each other, and are disposed in a V shape such that a rib spacing on an axle fastening portion side is narrower than a rib spacing on a damper fastening portion side.

\* \* \* \* \*