

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12419056
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Chen; Tzu-Yu et al.

Integrated circuit and method for manufacturing the same

Abstract

A semiconductor device includes a semiconductor substrate, a memory gate, and a data storage element. The semiconductor substrate includes a memory well which has two source/drain regions and a channel region between the source/drain regions. The memory gate is disposed above the channel region. The data storage element includes a ferroelectric material, and is disposed around the memory gate to separate the memory gate from the channel region.

Inventors: Chen; Tzu-Yu (Hsinchu, TW), Shih; Sheng-Hung (Hsinchu, TW), Tu; Kuo-Chi (Hsinchu, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Family ID: 1000008818128

Assignee: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Appl. No.: 18/354768

Filed: July 19, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230363176 A1	Nov. 09, 2023

Related U.S. Application Data

continuation parent-doc US 17332607 20210527 US 11751401 child-doc US 18354768

Publication Classification

Int. Cl.: **H10D30/01** (20250101); **H10B51/30** (20230101); **H10B51/40** (20230101); **H10D30/69** (20250101); **H10D64/01** (20250101); **H10D64/68** (20250101)

U.S. Cl.:

CPC **H10B51/30** (20230201); **H10B51/40** (20230201); **H10D30/0415** (20250101); **H10D30/701** (20250101); **H10D64/033** (20250101); **H10D64/689** (20250101);

Field of Classification Search

CPC: H10B (51/30); H10B (51/40); H10D (30/0415); H10D (30/701); H10D (64/033); H10D (64/689)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8053323	12/2010	Lin et al.	N/A	N/A
8883624	12/2013	Ramkumar	N/A	N/A
2016/0155748	12/2015	Li et al.	N/A	N/A
2016/0225867	12/2015	Kim	N/A	N/A

Primary Examiner: Li; Meiya

Attorney, Agent or Firm: Birch, Stewart, Kolasch & Birch, LLP

Background/Summary

REFERENCE TO RELATED APPLICATION (1) This application is a continuation of U.S. patent application Ser. No. 17/332,607, filed on May 27, 2021, the contents of which is incorporated herein by reference in its entirety.

BACKGROUND

(1) An integrated circuit (IC) is an electronic device which may include many functional elements, such as transistors, capacitors, resistors, and/or ferroelectric dynamic random access memories (FeDRAMs). There is a continuous need to further simplify and improve a process for manufacturing the ICs.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIGS. 1A to 1D are flow diagrams illustrating a method for manufacturing an integrated circuit in accordance with some embodiments.

(3) FIGS. 2 to 40 are schematic views illustrating intermediate stages of the manufacturing method

in accordance with some embodiments as depicted in FIGS. 1A to 1D.

(4) FIG. 41 illustrates a schematic top view of an integrated circuit in accordance with some embodiments.

(5) FIGS. 42 and 43 are schematic cross-sectional views taken along line B-B in an X direction and line C-C in a Y direction of FIG. 41, respectively.

DETAILED DESCRIPTION

(6) The following disclosure provides many different embodiments, or examples, for implementing different features of the disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(7) Further, spatially relative terms, such as “on,” “above,” “top,” “upper,” “lower,” “over,” “beneath,” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(8) The present disclosure is directed to an integrated circuit (IC), and methods for manufacturing the same. The IC may include ferroelectric dynamic random access memory (FeDRAM) devices, logic devices, and a boundary isolation structure between the FeDRAM devices and the logic devices. According to some methods for manufacturing the IC, after a ferroelectric layer of each FeDRAM device and a logic high-k (HK) dielectric of each logic device are formed, a memory active gate of each FeDRAM device is formed on the ferroelectric layer using a replacement gate (RPG) process, and a logic active gate of each logic device is formed on the logic HK dielectric using another RPG process. Such methods may be referred to as HK first methods.

(9) A challenge with the HK first methods is that the ferroelectric layer and/or the logic HK dielectric may be damaged by an etchant, such as hydrofluoric acid (HF) or other chemicals. In addition, when patterning the logic multiple films, a logic HK dielectric layer which is used for forming the logic HK dielectric may not be fully removed from a slanted sidewall of the boundary isolation structure.

(10) FIGS. 1A to 1D are flow diagrams illustrating a method 100 for manufacturing an IC in accordance with some embodiments. The method 100 may be called as a HK last method. FIGS. 2 to 40 illustrate schematic views of the intermediate stages of the method 100.

(11) Referring to FIGS. 1A and 2, the method 100 begins at step 101, where a first pad layer 21 and a second pad layer 22 are sequentially formed on a semiconductor substrate 200. The semiconductor substrate 200 includes a memory substrate region 201, a logic substrate region 202, and a boundary substrate region 203 between the memory substrate region 201 and the logic substrate region 202. In some embodiments, the semiconductor substrate 200 may be or may include a bulk silicon substrate, a silicon-on-insulator substrate (SOI), or other suitable semiconductor materials. The first pad layer 21 and the second pad layer 22 may be made from different dielectric materials. For example, the first pad layer 21 may include silicon oxide, and the second pad layer 22 may include silicon nitride. Other suitable dielectric materials for the first pad layer 21 and the second pad layer 22 are within the contemplated scope of the present disclosure. Each of the first pad layer 21 and the second pad layer 22 may be deposited by, for example, but

not limited to, chemical vapor deposition (CVD), physical vapor deposition (PVD), atomic layer deposition (ALD), thermal oxidation, or other suitable techniques.

(12) Referring to FIGS. 1A and 3, the method **100** proceeds to step **102**, where a patterning process is conducted to form trenches **23**, **24**, **25** respectively in the memory substrate region **201**, the logic substrate region **202**, and the boundary substrate region **203**. Step **102** may include (i) forming a patterned mask (not shown) on the second pad layer **22** to partially expose the second pad layer **22**, (ii) etching the second pad layer **22**, the first pad layer **21**, and the semiconductor substrate **200** through the patterned mask to form the trenches **23**, **24**, **25**, and (iii) removing the patterned mask. The etching may be implemented using dry etching, wet etching, or a combination thereof. The patterned mask may include a photoresist material or other suitable mask material, and may be formed by coating a photoresist layer, soft-baking, exposing the photoresist layer through a photomask, post-exposure baking, and developing the photoresist layer, followed by hard-baking to thereby form the patterned mask.

(13) Referring to FIGS. 1A and 4, the method **100** proceeds to step **103**, where first isolations **230**, a second isolation **240**, and a third isolation **250** are respectively formed in the trenches **23**, **24**, **25** shown in FIG. 3. Step **103** may include (i) depositing a dielectric layer (not shown) over the structure of FIG. 3 to fill the trenches **23**, **24**, **25**, and (ii) conducting a planarization process, such as a chemical mechanical polishing (CMP) process or other suitable techniques, to remove the dielectric layer on the second pad layer **22** so as to obtain the first, second, and third isolations **230**, **240**, **250**. Each of the first, second, and third isolations **230**, **240**, **250** may include, for example, silicon oxide. Other suitable materials for the first, second, and third isolations **230**, **240**, **250** are within the contemplated scope of the present disclosure.

(14) Referring to FIGS. 1A and 5, the method **100** proceeds to step **104**, where the first, second, and third isolations **230**, **240**, **250** shown in FIG. 4 are recessed to form memory isolations **231**, a logic isolation **241**, and a boundary isolation **251**. In some embodiments, step **104** may be implemented by immersing the structure of FIG. 4 in an etchant, for example, hydrofluoric acid (HF). Other suitable processes may be used for recessing the first, second, and third isolations **230**, **240**, **250**. Each of the memory isolations **231**, the logic isolation **241**, and the boundary isolation **251** may independently be or include, for example, a shallow trench isolation (STI) structure, a deep trench isolation (DTI) structure, or other suitable isolation structures.

(15) Referring to FIGS. 1A and 6, the method **100** proceeds to step **105**, where the second pad layer **22** shown in FIG. 5 is removed. Step **105** may be implemented using, for example, dry etching, wet etching, or a combination thereof, to selectively remove the second pad layer **22**. In some embodiments, step **105** may be implemented by immersing the structure of FIG. 5 in an etchant, for example, phosphoric acid (H.sub.3PO.sub.4). Other suitable processes may be used to remove the second pad layer **22**.

(16) Referring to FIGS. 1A and 7, the method **100** proceeds to step **106**, a memory well **26** is formed at the memory substrate region **201** overlying a bulk semiconductor region **200a** of the semiconductor substrate **200**, and a first logic well **27** and a second logic well **28** are separately formed at the logic substrate region **202** overlying the bulk semiconductor region **200a**. The memory well **26** is located at one side of the boundary isolation **251**, and the first logic well **27** and the second logic well **28** are located at the other side of the boundary isolation **251**. The memory well **26**, the first logic well **27**, and the second logic well **28** may be formed using ion implantation or other suitable techniques. The memory well **26** has a different doping type or concentration from the bulk semiconductor region **200a**. Each of the first logic well **27** and the second logic well **28** has a different doping type or concentration from the bulk semiconductor region **200a**. The memory well **26** may have a first conductivity type, and each of the first and second logic wells **27**, **28** may have the first conductivity type or a second conductivity type opposite to the first type conductivity. In some embodiments, the memory well **26** is n-type or p-type, the first logic well **27** is p-type, and the second logic well **28** is n-type. In alternative embodiments, the memory well **26**

is n-type or p-type, and both the first logic well **27** and the second logic well **28** are n-type or p-type. Other suitable variations for conductivity types of the memory well **26**, the first logic well **27** and the second logic well **28** are within the contemplated scope of the present disclosure.

(17) Referring to FIGS. **1A** and **8**, the method **100** proceeds to step **107**, where the first pad layer **21** shown in FIG. **7** is removed. Step **107** may be implemented using an etching process, such as dry etching, wet etching, or a combination thereof. Other suitable processes may be used for removing the first pad layer **21**.

(18) Referring to FIGS. **1A** and **9**, the method **100** proceeds to step **108**, where a dummy dielectric layer **29**, a dummy gate layer **30**, and a hard mask layer **31** are sequentially formed on the structure of FIG. **8**. The dummy dielectric layer **29** may include, for example, silicon oxide. The dummy gate layer **30** may include, for example, polysilicon. The hard mask layer **31** may include, for example, silicon oxide, silicon nitride, or silicon oxynitride. Other suitable materials for the dummy dielectric layer **29**, the dummy gate layer **30**, and the hard mask layer **31** are within the contemplated scope of the present disclosure. In some embodiments, the hard mask layer **31** includes a lower nitride layer **311** (including silicon nitride) and an upper oxide layer **312** (including silicon oxide). Each of the dummy dielectric layer **29**, the dummy gate layer **30**, and the hard mask layer **31** may be deposited by, for example, but not limited to, CVD, PVD, ALD, thermal oxidation, or other suitable techniques.

(19) Referring to FIGS. **1A** and **10**, the method **100** proceeds to step **109**, where a first patterned mask **32** is formed over the structure of FIG. **9**. The first patterned mask **32** has a pattern corresponding to a layout of a dummy memory structure **33**, a dummy wall **34**, a first dummy logic structure **35**, and a second dummy logic structure **36** which are shown in FIG. **11** and are formed in the subsequent step **110**. The materials and processes for the first patterned mask **32** are similar to those for the patterned mask described in step **102**, and therefore, the details thereof are omitted for the sake of brevity.

(20) Referring to FIGS. **1A** and **11**, the method **100** proceeds to step **110**, where the hard mask layer **31**, the dummy gate layer **30**, and the dummy dielectric layer **29** are patterned through the first patterned mask **32** shown in FIG. **10** to form the dummy memory structure **33**, the dummy wall **34**, the first dummy logic structure **35**, and the second dummy logic structure **36**. Step **110** may be implemented using dry etching, wet etching, or a combination thereof. After step **110**, the first patterned mask **32** may be removed. Other suitable techniques may be used for patterning the hard mask layer **31**, the dummy gate layer **30**, and the dummy dielectric layer **29**. The dummy wall **34** at the boundary substrate region **203** may be formed on the boundary isolation **251** in some embodiments, and may be formed on the bulk semiconductor region **200a** in alternative embodiments. In some embodiments, the dummy wall **34** may have a rectangular cross section.

(21) Referring to FIGS. **1B** and **12**, the method **100** proceeds to step **111**, where four pairs of first sidewall spacers **371**, **372**, **373**, **374** are formed. Each pair of the first sidewall spacers **371**, **372**, **373**, **374** are respectively formed at two lateral sides of a corresponding one of the dummy memory structure **33**, the first dummy logic structure **35**, the second dummy logic structure **36**, and the dummy wall **34**. Step **111** includes (i) depositing a first spacer material (not shown) over the structure of FIG. **11** using, for example, CVD, PVD, ALD, or other suitable deposition techniques, and (ii) anisotropically etching (e.g., dry etching, wet etching, a combination thereof, or other suitable etching techniques) the first spacer material to thereby form the first sidewall spacers **371**, **372**, **373**, **374**. The first sidewall spacers **371**, **372**, **373**, **374** may include, for example, silicon nitride. Other suitable materials for the first sidewall spacers **371**, **372**, **373**, **374** are within the contemplated scope of the present disclosure.

(22) Referring to FIGS. **1B** and **13**, the method **100** proceeds to step **112**, where three pairs of lightly doped regions **381**, **382**, **383** are formed. Each pair of the lightly doped regions **381**, **382**, **383** are formed in two lateral regions of a corresponding one of the memory well **26**, the first logic well **27**, and the second logic well **28**, respectively, and may have a conductivity type opposite to

that of the corresponding one of the memory well **26**, the first logic well **27**, and the second logic well **28**. In step **112**, the two lateral regions of each of the memory well **26**, the first logic well **27**, and the second logic well **28** are exposed from and non-covered by (i) a corresponding one of the dummy memory structure **33**, the first dummy logic structure **35**, and the second dummy logic structure **36**, and (ii) a corresponding pair of the first sidewall spacers **371**, **372**, **373**. The lightly doped regions **381**, **382**, **383** may be formed using ion implantation, or other suitable techniques. In some embodiments, each of the lightly doped regions **381**, **382**, **383** may be a lightly doped source/drain (LDD).

(23) Referring to FIGS. **1B** and **14**, the method **100** proceeds to step **113**, where four pairs of second sidewall spacers **391**, **392**, **393**, **394** are formed. Each pair of the second sidewall spacers **391**, **392**, **393**, **394** are formed on a corresponding pair of the first sidewall spacers **371**, **372**, **373**, **374**, respectively. Step **113** includes (i) depositing a second spacer material (not shown) over the structure of FIG. **13** using, for example, CVD, PVD, ALD, or other suitable deposition techniques, and (ii) anisotropically etching (e.g., dry etching, wet etching, a combination thereof, or other suitable etching techniques) the second spacer material to form the second sidewall spacers **391**, **392**, **393**, **394**. The second sidewall spacers **391**, **392**, **393**, **394** may include, for example, silicon oxynitride. Other suitable materials for the second sidewall spacers **391**, **392**, **393**, **394** are within the contemplated scope of the present disclosure. Each pair of the second sidewall spacers **391**, **392**, **393** are formed to partially cover a corresponding pair of the lightly doped regions **381**, **382**, **383**, respectively.

(24) Referring to FIGS. **1B** and **15**, the method **100** proceeds to step **114**, where three pairs of source/drain regions **401**, **402**, **403** are formed. Each pair of the source/drain regions **401**, **402**, **403** are formed in the two lateral regions of a corresponding one of the memory well **26**, the first logic well **27** and the second logic well **28**, respectively, and may have a conductivity type opposite to that of the corresponding one of the memory well **26**, the first logic well **27** and the second logic well **28**. In some embodiments, the source/drain regions **401**, **402**, **403** serve as memory source/drain regions, first logic source/drain regions, and second logic source/drain regions, respectively. In step **114**, the two lateral regions of each of the memory well **26**, the first logic well **27**, and the second logic well **28** are exposed from and non-covered by (i) a corresponding one of the dummy memory structure **33**, the first dummy logic structure **35**, and the second dummy logic structure **36**, (ii) a corresponding pair of the first sidewall spacers **371**, **372**, **373**, and (iii) a corresponding pair of the second sidewall spacers **391**, **392**, **393**. Each pair of the source/drain regions **401**, **402**, **403** may be located to respectively and partially overlap a corresponding pair of the lightly doped regions **381**, **382**, **383**, and may have a conductivity type which is the same as that of a corresponding pair of the lightly doped regions **381**, **382**, **383**. Each pair of the source/drain regions **401**, **402**, **403** may be p-type or n-type doped regions, and may have a doping concentration greater than that of a corresponding pair of the lightly doped regions **381**, **382**, **383**, respectively. Each pair of the source/drain regions **401**, **402**, **403** may be formed using ion implantation, or other suitable techniques. After step **114**, a memory channel region **261** is formed between the memory source/drain regions **401**, a first logic channel region **271** is formed between the first logic source/drain regions **402**, and a second logic channel region **281** is formed between the second logic source/drain regions **403**. Each of the lightly doped regions **381** is disposed between the memory channel region **261** and a corresponding one of the memory source/drain regions **401**. Each of the lightly doped regions **382** is disposed between the first logic channel region **271** and a corresponding one of the first logic source/drain regions **402**. Each of the lightly doped regions **383** is disposed between the second logic channel region **281** and a corresponding one of the second logic source/drain regions **403**.

(25) Referring to FIGS. **1B** and **16**, the method **100** proceeds to step **115**, where the patterned hard mask layer **31**, an upper portion of each of the first sidewall spacers **371**, **372**, **373**, **374**, and an upper portion of each of the second sidewall spacers **391**, **392**, **393**, **394** are removed. Step **115** may

be implemented using a planarization process, such as a CMP process or other suitable processes. (26) Referring to FIGS. 1B and 17, the method 100 proceeds to step 116, where a planarized contact etch stop layer (planarized CESL) 41 and a planarized first dielectric layer 42 are sequentially formed after step 115. Step 116 includes (i) conformally depositing a CESL (not shown) over the structure of FIG. 16 using, for example, CVD, plasma-enhanced chemical vapor deposition (PECVD), ALD, spin-on coating, electroless plating, or other suitable deposition techniques, (ii) conformally depositing a first dielectric layer (not shown) on the non-shown CESL using, for example, CVD, PVD, or other suitable deposition techniques, and (iii) conducting a planarization process, such as a CMP process or other suitable processes, to remove the excess CESL and the excess first dielectric layer to expose the patterned dummy gate layer 30, thereby forming the planarized CESL 41 and the planarized first dielectric layer 42. The planarized CESL 41 may include, but not limited to, metal nitride, metal oxide, metal carbide, silicon nitride, silicon oxide, silicon carbide, silicon oxynitride, or combinations thereof. Other suitable materials for the planarized CESL 41 are within the contemplated scope of the present disclosure. The planarized first dielectric layer 42 may include, but not limited to, silicon oxide, silicon nitride, silicon carbide, silicon oxycarbide, silicon oxynitride, silicon carbonitride, silicon oxycarbonitride, undoped silicate glass (USG), phosphosilicate glass (PSG), borosilicate glass (BSG), boron-doped phosphosilicate glass (BPSG), fluorine-doped silicate glass (FSG), extreme low dielectric constant (k) material, other suitable dielectric materials, or combinations thereof.

(27) Referring to FIGS. 1B and 18, the method 100 proceeds to step 117, where portions of the patterned dummy gate layer 30 and portions of the patterned dummy dielectric layer 29 (see FIG. 17) at the dummy memory structure 33, the first dummy logic structure 35, and the second dummy logic structure 36 are removed. Step 117 may include (i) forming a patterned mask (not shown) over the structure of FIG. 17 to expose the portions of the patterned dummy gate layer 30, (ii) etching the dummy gate layer 30 and the dummy dielectric layer 29 through the patterned mask, and (iii) removing the patterned mask. The etching may be implemented using dry etching, wet etching, or a combination thereof. The patterned mask may be similar to that described in step 102. After step 117, a patterned dielectric structure is formed on the semiconductor substrate 200, and includes the planarized first dielectric layer 42, the planarized CESL 41, and the sidewall spacers 371-374, 391-394 (see FIG. 16). A first recess 33a which exposes the memory channel region 261 and two second recesses 35a, 36a which expose the logic channel regions 271, 281 are formed in the patterned dielectric structure.

(28) Referring to FIGS. 1B and 19, the method 100 proceeds to step 118, where a ferroelectric layer 43 is conformally formed over the structure of the FIG. 18. The ferroelectric layer 43 includes a ferroelectric material, and may include binary oxides, ternary oxides, quaternary oxides, other suitable oxides, or combinations thereof. The binary oxides may include, for example, but not limited to, hafnium oxide (hafnia, HfO_2) or other suitable materials. The ternary oxides may include, for example, but not limited to, hafnium silicate (HfSiO_x), hafnium zirconate (HfZrO_x), barium titanate (BaTiO_3), lead titanate (PbTiO_3), strontium titanate (SrTiO_3), calcium manganite (CaMnO_3), bismuth ferrite (BiFeO_3), aluminum scandium nitride (AlScN), aluminum gallium nitride (AlGaN), aluminum yttrium nitride (AlYN), doped HfO_2 (the dopants may include Si, La, Y, Sc, Ga, Gd, combinations thereof, or other suitable dopants), other suitable materials, or combinations thereof. The quaternary oxides may include, for example, but not limited to, lead zirconate titanate ($\text{PbZr}_{0.5}\text{Ti}_{0.5}\text{O}_3$), barium strontium titanate (BaSrTiO_3), strontium bismuth tantalate ($\text{SrBi}_2\text{Ta}_2\text{O}_{10}$), or combinations thereof. Other suitable ferroelectric materials for the ferroelectric layer 43 are within the contemplated scope of the present disclosure. The ferroelectric layer 43 may be formed using, for example, CVD, PVD, ALD, plasma-enhanced ALD, molecular beam epitaxy (MBE), or other suitable deposition techniques. In some embodiments, the ferroelectric layer 43 may have a thickness ranging from about 50 Å to about 150 Å. In some embodiments, before forming the

ferroelectric layer **43**, a first interfacial layer **44** may be optionally formed in the memory well **26**, the first logic well **27**, and the second logic well **28** using, for example, thermal oxidation, or other suitable techniques. In some embodiments, the ferroelectric layer **43** is conformally deposited over the patterned dielectric structure along the surface of the first recess **33a** and along the surfaces of the second recesses **35a**, **36a**.

(29) Referring to FIGS. **1B** and **20**, the method **100** proceeds to step **119**, where a first barrier layer **45** is conformally formed over the structure of FIG. **19**. The first barrier layer **45** may include titanium nitride. Other suitable materials for the first barrier layer **45** are within the contemplated scope of the present disclosure. The first barrier layer **45** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques. The provision of the first barrier layer **45** may prevent direct annealing of the ferroelectric layer **43** in a subsequent process, and may prevent oxygen gas from being in contact with the ferroelectric layer **43** and the first interfacial layer **44**.

(30) Referring to FIGS. **1C** and **21**, the method **100** proceeds to step **120**, where a first cap layer **46** is conformally formed over the structure of FIG. **20**. The first cap layer **46** may include silicon. The other suitable materials for the first cap layer **46** are within the contemplated scope of the present disclosure. The first cap layer **46** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques. The provision of the first cap layer **46** may prevent oxidation of the first barrier layer **45**, and the provision of the first barrier layer **45** may also prevent silicon in the first cap layer **46** from being reacted with the ferroelectric layer **43**.

(31) Referring to FIGS. **1C** and **22**, the method **100** proceeds to step **121**, where a second patterned mask **47** is formed over the structure of FIG. **21** to cover the layers on the memory substrate region **201** and to expose the layers on the logic substrate region **202** and the boundary substrate region **203**. In some embodiments, the second patterned mask **47** is formed to fully cover the layers above the memory well **26**. The materials and processes for the second patterned mask **47** are similar to those for the patterned mask described in step **102**, and therefore, the details thereof are omitted for the sake of brevity.

(32) Referring to FIGS. **1C** and **23**, the method **100** proceeds to step **122**, where portions of the ferroelectric layer **43**, the first barrier layer **45**, and the first cap layer **46** which are exposed from the second patterned mask **47** are removed. In addition, portions of the first interfacial layer **44** in the logic substrate region **202** shown in FIG. **22**, if any, are also removed. Step **122** may be implemented using, for example, dry etching, wet etching, or a combination thereof. Afterwards, the second patterned mask **47** is removed. In some embodiments, in step **122**, the ferroelectric layer **43** shown in FIG. **22** is partially removed such that a first ferroelectric portion of the ferroelectric layer **43** is left on the memory substrate region **201**.

(33) Referring to FIGS. **1C** and **24**, the method **100** proceeds to step **123**, where a gate dielectric layer **48** is conformally formed over the structure of FIG. **23**. The gate dielectric layer **48** may include, but not limited to, tantalum oxide (Ta.sub.2O.sub.5), titanium oxide (TiO.sub.2), hafnium oxide (HfO.sub.2), aluminum oxide (Al.sub.2O.sub.3), zirconium oxide (ZrO.sub.2), hafnium silicate (HfSiO.sub.x), zirconium silicate (ZrSiO.sub.4), lanthanum oxide (La.sub.2O.sub.3), praseodymium oxide (Pr.sub.2O.sub.3), other suitable high-k materials, or combinations thereof. Other suitable materials for the gate dielectric layer **48** are within the contemplated scope of the present disclosure. The gate dielectric layer **48** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques. In some embodiments, the gate dielectric layer **48** may have a thickness ranging from about 5 Å to about 30 Å. In some embodiments, before forming the gate dielectric layer **48**, a second interfacial layer **49** may be optionally formed in the first logic well **27** and the second logic well **28** using, for example, thermal oxidation, or other suitable techniques. In some embodiments, the gate dielectric layer **48** is conformally deposited over the patterned dielectric structure, on the first ferroelectric portion of the ferroelectric layer **43**, and along the surfaces of the second recesses **35a**, **36a** (See FIG. **18**).

(34) Referring to FIGS. **1C** and **25**, the method **100** proceeds to step **124**, where a second barrier

layer **50** is conformally formed over the structure of FIG. **24**. The second barrier layer **50** may include titanium nitride. Other suitable materials for the second barrier layer **50** are within the contemplated scope of the present disclosure. The second barrier layer **50** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques. The provision of the second barrier layer **50** may prevent direct annealing of the gate dielectric layer **48** in a subsequent process, and may prevent oxygen gas from being in contact with the gate dielectric layer **48** and the second interfacial layer **49**.

(35) Referring to FIGS. **1C** and **26**, the method **100** proceeds to step **125**, where a second cap layer **51** is conformally formed over the structure of FIG. **25**. The second cap layer **51** may include silicon. The other suitable materials for the second cap layer **51** are within the contemplated scope of the present disclosure. The second cap layer **51** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques. In some embodiments, an annealing treatment may be optionally implemented after step **125**. The provision of the second cap layer **51** may prevent oxidation of the second barrier layer **50**, and the provision of the second barrier layer **50** may also prevent silicon in the second cap layer **51** from being reacted with the gate dielectric layer **48**.

(36) Referring to FIGS. **1C** and **27**, the method **100** proceeds to step **126**, where a third patterned mask **52** is formed over the structure of FIG. **26** to cover the layers on the logic substrate region **202** and the boundary substrate region **203** and to expose the layers on the memory substrate region **201**. In some embodiments, the layers on the memory well **26** are exposed from the third patterned mask **52**. The materials and processes for the third patterned mask **52** are similar to those for the patterned mask described in step **102**, and the details thereof hence are omitted for the sake of brevity.

(37) Referring to FIGS. **1C** and **28**, the method **100** proceeds to step **127**, where portions of the second cap layer **51**, the second barrier layer **50**, and the gate dielectric layer **48** which are exposed from the third patterned mask **52** (see FIG. **27**) are removed. Step **127** may be implemented using, for example, dry etching, wet etching, or a combination thereof. Afterwards, the third patterned mask **52** is removed.

(38) Referring to FIGS. **1C** and **29**, the method **100** proceeds to step **128**, where the first cap layer **46** and the second cap layer **51** are removed. In addition, portions of the gate dielectric layer **48** and the second barrier layer **50** disposed between the first cap layer **46** and the second cap layer **51** may also be removed. Step **128** may be implemented using, for example, dry etching, wet etching, or a combination thereof.

(39) Referring to FIGS. **1D** and **30**, the method **100** proceeds to step **129**, where an etch stop layer **53** is conformally formed over the structure of FIG. **29**. The etch stop layer **53** may include tantalum nitride. Other suitable materials for the etch stop layer **53** are within the contemplated scope of the present disclosure. The etch stop layer **53** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques.

(40) Referring to FIGS. **1D** and **31**, the method **100** proceeds to step **130**, where a P metal layer **54** is conformally formed over the structure of FIG. **30**. The P metal layer **54** may include titanium nitride. Other suitable materials for the P metal layer **54** are within the contemplated scope of the present disclosure. The P metal layer **54** may be formed using, for example, CVD, PVD, ALD, or other suitable techniques.

(41) Referring to FIGS. **1D** and **32**, the method **100** proceeds to step **131**, where a protective layer **55** is formed over the structure of FIG. **31**. Step **131** may include (i) depositing a dielectric material layer over the structure of FIG. **31**, and (ii) conducting a planarization process, such as a CMP process or other suitable techniques, so as to obtain the protective layer **55**. The protective layer **55** may include a dielectric material, for example, spin on glass (SOG, a silicon oxide based polysiloxane). Other suitable materials for the protective layer **55** are within the contemplated scope of the present disclosure.

(42) Referring to FIGS. **1D** and **33**, the method **100** proceeds to step **132**, where the protective

layer **55** is partially removed to leave first, second, and third protective portions **551**, **552**, **553** of the protective layer **55** respectively above the memory well **26**, the first logic well **27**, and the second logic well **28** and to expose upper portions of the P metal layer **54**. Step **132** may be implemented by using, for example, dry etching, wet etching, or a combination thereof. Other suitable techniques may be used for partially removal of the protective layer **55**.

(43) Referring to FIGS. **1D** and **34**, the method **100** proceeds to step **133**, where a fourth patterned mask **56** is formed over the structure of FIG. **33** to expose the first and third protective portions **551**, **553**. The materials and processes for the fourth patterned mask **56** are similar to those for the patterned mask described in step **102**, and the details thereof are hence omitted for the sake of brevity.

(44) Referring to FIGS. **1D** and **35**, the method **100** proceeds to step **134**, where the first and third protective portions **551**, **553** are removed through the fourth patterned mask **56** shown in FIG. **34**. Step **134** may be implemented by using, for example, dry etching, wet etching, or a combination thereof. Afterwards, the fourth patterned mask **56** is removed.

(45) Referring to FIGS. **1D** and **36**, the method **100** proceeds to step **135**, where the P metal layer **54** shown in FIG. **35** is removed to expose the etch stop layer **53**, thereby leaving a P metal portion **541** which is disposed between the second protective portion **552** and the etch stop layer **53**. Step **135** may be implemented by using, for example, dry etching, wet etching, or a combination thereof.

(46) Referring to FIGS. **1D** and **37**, the method **100** proceeds to step **136**, where the second protective portion **552** shown in FIG. **36** is removed. Step **136** may be implemented by using, for example, dry etching, wet etching, or a combination thereof.

(47) Referring to FIGS. **1D** and **38**, the method **100** proceeds to step **137**, where a metal fill layer **57** is formed over the structure of FIG. **37** to fill the first and second recesses **33a**, **35a**, **36a** (see FIG. **18**) located respectively above the memory well **26**, the first logic well **27**, and the second logic well **28**. The metal fill layer **57** may include, but not limited to, tungsten, platinum, aluminum copper, gold, titanium, tantalum, tantalum nitride, tungsten nitride, tantalum aluminum carbide, other suitable materials, alloys thereof, or combinations thereof. The metal fill layer **57** may be formed using, for example, CVD, PVD, electroless plating or other suitable techniques. In some embodiments, the metal fill layer **57** is an N metal layer.

(48) Referring to FIGS. **1D** and **39**, the method **100** proceeds to step **138**, where the metal fill layer **57** is planarized to a point that an uppermost surface of the planarized first dielectric layer **42** is exposed, thereby forming a memory device (e.g., a FeDRAM device) **91**, a first logic device **92** and a second logic device **93**. The dummy wall **34** is located between the memory device **91** and the first logic device **92**. The memory device **91** is at the memory substrate region **201**, and the first and second logic devices **92**, **93** are at the logic substrate region **202**. The metal fill layer **57** may be planarized using, for example, CMP, or other suitable techniques. After step **138**, an excess of the metal fill layer **57** is removed to form (i) a memory gate **57a** in the first recess **33a** (see FIG. **18**) above the memory channel region **261** in the memory device **91**, (ii) a first logic gate **57b** in the second recess **35a** (see FIG. **18**) above the first channel region **271** in the first logic device **92**, and (iii) a second logic gate **57c** in the second recess **36a** (see FIG. **18**) above the second channel region **281** in the second logic device **93**. In addition, after step **138**, an excess of the first ferroelectric portion of the ferroelectric layer **43** shown in FIG. **38** is removed such that a region of the first ferroelectric portion is left on the surface of the first recess **33a** to form a data storage element **43a** of the memory device **91**. The data storage element **43a** includes a ferroelectric material, and is disposed around the memory gate **57a** to separate the memory gate **57a** from the memory channel region **261**. In some embodiments, the data storage element **43a** may have a thickness ranging from about 50 Å to about 150 Å. In some embodiments, the data storage element **43a** may have a U-shape cross section. An excess portion of the gate dielectric layer **48** shown in FIG. **38** is removed such that two portions of the gate dielectric layer **48** are respectively left on the surfaces of the second recesses **35a**, **36a** to form a first gate dielectric **48a** in the first logic device **92** and a second

gate dielectric **48b** in the second logic device **93**. The first gate dielectric **48a** is disposed around the first logic gate **57b** to separate the first logic gate **57b** from the first logic channel region **271**. The second gate dielectric **48b** is disposed around the second logic gate **57c** to separate the second logic gate **57c** from the second logic channel region **281**. In some embodiments, each of the first gate dielectric **48a** and the second gate dielectric **48b** may include tantalum oxide (Ta.sub.2O.sub.5), titanium oxide (TiO.sub.2), hafnium oxide (HfO.sub.2), aluminum oxide (Al.sub.2O.sub.3), zirconium oxide (ZrO.sub.2), hafnium silicate (HfSiO.sub.x), zirconium silicate (ZrSiO.sub.4), lanthanum oxide (La.sub.2O.sub.3), praseodymium oxide (Pr.sub.2O.sub.3), or combinations thereof. In some embodiments, each of the first gate dielectric **48a** and the second gate dielectric **48b** may have a thickness ranging from 5 Å to 30 Å. The first barrier layer **45** shown in FIG. **38** is formed into a barrier portion **45a**. The second barrier layer **50** shown in FIG. **38** is formed into two barrier portions **50a**, **50b** respectively in the first and the second logic devices **92**, **93**. The etch stop layer **53** shown in FIG. **38** is formed into a first etch stop portion **53a** in the memory device **91**, a second etch stop portion **53b** in the first logic device **92**, and a third etch stop portion **53c** in the second logic device **93**. In some embodiments, a memory gate structure of the memory device **91** may include the memory gate **57a**, the data storage element **43a**, the first interfacial layer **44**, the barrier portion **45a**, and the first etch stop portion **53a**. A first gate structure of the first logic device **92** may include the first logic gate **57b**, the first gate dielectric **48a**, the second interfacial layer **49** on the first logic well **27**, the barrier portion **50a**, the second etch stop portion **53b**, and the P metal portion **541**. A second gate structure of the second logic device **93** may include the second logic gate **57c**, the second gate dielectric **48b**, the second interfacial layer **49** on the second logic well **28**, the barrier portion **50b**, and the third etch stop portion **53c**. In some embodiments, the memory gate structure and the first and second gate structures may have substantially the same height. In some embodiments, the memory device **91** is an N-FeDRAM device, the first logic device **92** is a PFET device, and the second logic device **93** is an NFET device. In some embodiments, the first logic device **92** is a p-type transistor, and the P metal portion **541** is disposed between the first gate dielectric **48a** and the first logic gate **57b**.

(49) Referring to FIGS. **1D** and **40**, the method **100** proceeds to step **139**, where an interconnect feature is formed on the structure shown in FIG. **39**. The interconnect feature includes a second dielectric layer **58**, three pairs of source/drain contacts **591**, **592**, **593**, a third dielectric layer **6**, and metal lines **7**. The second dielectric layer **58** is formed on the structure shown in FIG. **39**. The materials and deposition for the second dielectric layer **58** may be similar to those for the planarized first dielectric layer **42**, and the details thereof are hence omitted for the sake of brevity. After the formation of the second dielectric layer **58**, the three pairs of the source/drain contacts **591**, **592**, **593** are formed to extend through the second dielectric layer **58**, the planarized first dielectric layer **42**, and the planarized CESL **41** to be in electrical contact with the three pairs of the source/drain regions **401**, **402**, **403**, respectively. The formation of the pairs of the source/drain contacts **591**, **592**, **593** may be implemented by (i) forming a patterned mask (not shown), (ii) etching the second dielectric layer **58**, the planarized first dielectric layer **42**, and the planarized CESL **41** to form three pairs of trenches (not shown) that expose the three pairs of the source/drain regions **401**, **402**, **403**, respectively, (iii) depositing a contact material on the second dielectric layer **58** to fill the trenches, and (iv) removing the excess contact material on the second dielectric layer **58**. In some embodiments, the deposition of the contact material may be implemented using, for example, CVD, PVD, electroless plating, electroplating, or other suitable deposition techniques. In some embodiments, the source/drain contacts **591**, **592**, **593** may include, but not limited to, copper, aluminum, tungsten, or combinations thereof. Other suitable materials for the source/drain contacts **591**, **592**, **593** are within the contemplated scope of the present disclosure. In some embodiments, the removal of the excess contact material may be implemented using, for example, CMP, or other suitable planarization techniques. In some embodiments, before the deposition of the pairs of the source/drain contacts **591**, **592**, **593**, three pairs of silicide pads **8a**, **8b**, **8c** may be

formed on the three pairs of the source/drain regions **401**, **402**, **403**, respectively. After the formation of the source/drain contacts **591**, **592**, **593**, the third dielectric layer **6** is formed on the second dielectric layer **58** and the source/drain contacts **591**, **592**, **593**. In some embodiments, the material and formation for the third dielectric layer **6** may be similar to those for the planarized first dielectric layer **42**, and the details thereof are hence omitted for the sake of brevity. After the formation of the third dielectric layer **6**, the metal lines **7** are formed in the third dielectric layer **6** such that the metal lines **7** are respectively in electrical contact with the source/drain contacts **591**, **592**, **593**. The formation for the metal lines **7** may be implemented by (i) patterning the third dielectric layer **6** to form recesses (not shown) to expose the source/drain contacts **591**, **592**, **593**, (ii) depositing a metallic material on the third dielectric layer **6** to fill the recesses, and (iii) removing the excess metallic material on the third dielectric layer **6**. In some embodiments, the third dielectric layer **6** is patterned using known photolithography and etching processes. In some embodiments, the deposition of the metallic material for the metal lines **7** may be implemented using, for example, CVD, PVD, electroless plating, electroplating, or other suitable deposition techniques. In some embodiments, the metal lines **7** may include, but not limited to, copper, aluminum, tungsten, or combinations thereof. Other suitable materials for the metal lines **7** are within the contemplated scope of the present disclosure. In some embodiments, the removal of the excess metallic material may be implemented using, for example, CMP, or other suitable planarization techniques. After step **139**, an integrated circuit (IC) **10A** is obtained. In alternative embodiments, other suitable methods may also be applied for forming the IC **10A**. In yet alternative embodiments, additional features may be added in the IC **10A**, and some features in the IC **10A** may be modified, replaced, or eliminated without departure of the spirit and scope of the present disclosure.

(50) Referring to FIG. **41**, in accordance with some embodiments, an IC **100a** includes the memory devices (e.g., FeDRAM devices) **91**, the dummy wall **34**, the first logic devices **92**, and the second logic devices **93**. The memory devices **91** are located within the memory substrate region **201**, and are surrounded by the dummy wall **34**. In some embodiments, FIG. **40** showing the IC **10A** may be a cross-sectional view taken along line A-A of FIG. **41**. FIG. **42** is a fragmentary cross-sectional view taken along line B-B in an X direction. FIG. **43** is a fragmentary cross-sectional view taken along line C-C in a Y direction transverse to the X direction. Two adjacent ones of the memory devices **91** in the Y direction may be separated from each other through a STI structure **200b** (see FIGS. **41** and **43**). The memory substrate region **201** may have a length (L1) in the X direction and a length (L2) in the Y direction. A distance between the memory substrate region **201** and the dummy wall **34** is represented as “d1,” and a distance between the dummy wall **34** and each of the first logic devices **92** is represented as “d2.” Each of the distances (d1, d2) may range from about 0.2 μm to about 0.5 μm . Each of the lengths (L1, L2) may range from about 50 μm to about 200 μm . A width (W) of the dummy wall **34** may vary with the variation of the distances (d1, d2). For example, if the distance (d1, d2) is a respective one of about 0.2 μm , about 0.3 μm , about 0.4 μm , and about 0.5 μm , the width (W) of the dummy wall **34** may be in a corresponding one of a range from about 0.6 μm to about 1.1 μm , a range from about 0.7 μm to about 1.2 μm , a range from about 0.8 μm to about 1.3 μm , and a range from about 0.8 μm to about 1.4 μm (namely, the larger the distance (d1, d2), the larger the lower and upper limits of the range of the width (W) of the dummy wall **34**). A number of the dummy wall **34** may vary with the variation of the lengths (L1, L2) of the memory substrate region **201**. For example, if the length (L1, L2) is a respective one of about 50 μm , about 100 μm , about 150 μm , and about 200 μm , the number of the dummy wall **34** may be a corresponding one of 1, 2, 3, and 4, respectively (namely, the larger the length (L1, L2), the larger the number of the dummy wall **34**).

(51) In this disclosure, an IC is made by a HK last method, and includes and integrates a memory device, a dummy wall, and first and second logic devices. Compared with an IC made by the HK first method, the data storage element of the memory device and the gate dielectrics of the first and

second logic devices of this disclosure are not adversely affected during etching, and an undesirable residue (e.g., high-k material residue) is not found within the IC. In some embodiments, the number of the dummy wall, which is at least one, may vary depending on the layout design of the IC, thereby effectively preventing dishing during planarization process (e.g., CMP).

(52) In accordance with some embodiments of the present disclosure, a semiconductor device includes a semiconductor substrate, a memory gate, and a data storage element. The semiconductor substrate includes a memory well which has two memory source/drain regions and a memory channel region between the memory source/drain regions. The memory gate is disposed above the memory channel region. The data storage element includes a ferroelectric material, and is disposed around the memory gate to separate the memory gate from the memory channel region.

(53) In accordance with some embodiments of the present disclosure, the ferroelectric material includes hafnium oxide, hafnium silicate, hafnium zirconate, barium titanate, lead titanate, strontium titanate, calcium manganite, bismuth ferrite, aluminum scandium nitride, aluminum gallium nitride, aluminum yttrium nitride, doped hafnium oxide, lead zirconate titanate, barium strontium titanate, strontium bismuth tantalate, or combinations thereof.

(54) In accordance with some embodiments of the present disclosure, the data storage element has a thickness ranging from 50 Å to 150 Å.

(55) In accordance with some embodiments of the present disclosure, the memory well further includes two lightly doped regions, each of which is disposed between the memory channel region and a corresponding one of the source/drain regions.

(56) In accordance with some embodiments of the present disclosure, the data storage element has a U-shape cross section.

(57) In accordance with some embodiments of the present disclosure, an integrated circuit includes a semiconductor substrate, a memory device, a logic device, and a dummy wall. The semiconductor substrate includes a memory substrate region, a logic substrate region, and a boundary substrate region between the memory substrate region and the logic substrate region. The memory device includes a memory well and a memory gate structure. The memory well is formed in the memory substrate region, and has two memory source/drain regions and a memory channel region between the memory source/drain regions. The memory gate structure includes a memory gate disposed above the memory channel region, and a data storage element including a ferroelectric material. The data storage element is disposed around the memory gate to separate the memory gate from the memory channel region. The logic device includes a logic well and a gate structure. The logic well is formed in the logic substrate region, and has two logic source/drain regions and a logic channel region between the logic source/drain regions. The gate structure includes a logic gate and a gate dielectric. The logic gate is disposed above the logic channel region. The gate dielectric is disposed around the logic gate to separate the logic gate from the logic channel region. The dummy wall is disposed on the boundary substrate region.

(58) In accordance with some embodiments of the present disclosure, the memory gate structure and the gate structure have the same height.

(59) In accordance with some embodiments of the present disclosure, the ferroelectric material includes hafnium oxide, hafnium silicate, hafnium zirconate, barium titanate, lead titanate, strontium titanate, calcium manganite, bismuth ferrite, aluminum scandium nitride, aluminum gallium nitride, aluminum yttrium nitride, doped hafnium oxide, lead zirconate titanate, barium strontium titanate, strontium bismuth tantalate, or combinations thereof.

(60) In accordance with some embodiments of the present disclosure, the data storage element has a thickness ranging from 50 Å to 150 Å.

(61) In accordance with some embodiments of the present disclosure, the gate dielectric includes tantalum oxide, titanium oxide, hafnium oxide, aluminum oxide, zirconium oxide, hafnium silicate, zirconium silicate, lanthanum oxide, praseodymium oxide, or combinations thereof.

(62) In accordance with some embodiments of the present disclosure, the gate dielectric has a thickness ranging from 5 Å to 30 Å.

(63) In accordance with some embodiments of the present disclosure, the logic device is a p-type transistor, and the gate structure further includes a P metal portion disposed between the gate dielectric and the logic gate.

(64) In accordance with some embodiments of the present disclosure, a method for manufacturing an integrated circuit includes: forming a boundary isolation in a semiconductor substrate; forming a memory well and a logic well in the semiconductor substrate, the memory well and the logic well being located at two opposite sides of the boundary isolation, the memory well having two memory source/drain regions and a memory channel region between the memory source/drain regions, the logic well having two logic source/drain regions and a logic channel region between the logic source/drain regions; forming a patterned dielectric structure on the semiconductor substrate, the patterned dielectric feature having a first recess which exposes the memory channel region, and a second recess which exposes the logic channel region; forming a data storage element along a surface of the first recess; forming a gate dielectric along a surface of the second recess; forming a memory gate in the first recess such that the data storage element is disposed around the memory gate; and forming a logic gate in the second recess such that the gate dielectric is disposed around the logic gate.

(65) In accordance with some embodiments of the present disclosure, the semiconductor substrate includes a memory substrate region, a logic substrate region, and a boundary substrate region between the memory substrate region and the logic substrate region. The boundary isolation is formed in the boundary substrate region, and the memory well and the logic well are formed in the memory substrate region and the logic substrate region, respectively.

(66) In accordance with some embodiments of the present disclosure, the formation of the data storage element includes: conformally depositing a ferroelectric layer over the patterned dielectric structure along the surface of the first recess and along the surface of the second recess; partially removing the ferroelectric layer such that a first ferroelectric portion of the ferroelectric layer is left on the memory substrate region; and removing an excess of the first ferroelectric portion such that a region of the first ferroelectric portion is left on the surface of the first recess to serve as the data storage element.

(67) In accordance with some embodiments of the present disclosure, the formation of the gate dielectric includes: conformally depositing a gate dielectric layer over the patterned dielectric structure, on the first ferroelectric portion, and along the surface of the second recess; and removing an excess of the gate dielectric layer such that a portion of the gate dielectric layer is left on the surface of the second recess to serve as the gate dielectric.

(68) In accordance with some embodiments of the present disclosure, the memory gate and the logic gate are formed simultaneously.

(69) In accordance with some embodiments of the present disclosure, the formation of the memory gate and the logic gate includes: depositing a metal fill layer on the gate dielectric layer to fill the first and second recesses; and removing an excess of the metal fill layer such that the metal fill layer is formed into the memory gate in the first recess and the logic gate in the second recess.

(70) In accordance with some embodiments of the present disclosure, removing the excess of the gate dielectric layer, removing the excess of the first ferroelectric portion, and removing the excess of the metal fill layer are implemented simultaneously.

(71) In accordance with some embodiments of the present disclosure, a P metal portion is further formed between the gate dielectric and the logic gate.

(72) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes or structures for carrying out the same purposes and/or achieving the same advantages of

the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A method for manufacturing an integrated circuit, comprising: forming a memory well and a logic well respectively in a memory substrate region and a logic substrate region of a semiconductor substrate, the memory well having two memory source/drain regions and a memory channel region between the two memory source/drain regions, the logic well having two logic source/drain regions and a logic channel region between the two logic source/drain regions; forming a patterned dielectric structure on the semiconductor substrate, the patterned dielectric structure having a first recess which exposes the memory channel region, and a second recess which exposes the logic channel region; forming a data storage element along a surface of the first recess; forming a gate dielectric along a surface of the second recess; forming a memory gate in the first recess such that the data storage element is disposed around the memory gate; and forming a logic gate in the second recess such that the gate dielectric is disposed around the logic gate, wherein the formation of the data storage element includes: conformally depositing a ferroelectric layer over the patterned dielectric structure along the surface of the first recess and along the surface of the second recess, partially removing the ferroelectric layer such that a first ferroelectric portion of the ferroelectric layer is left on the memory substrate region, and removing an excess of the first ferroelectric portion such that a region of the first ferroelectric portion is left on the surface of the first recess to serve as the data storage element; and wherein the formation of the gate dielectric includes: conformally depositing a gate dielectric layer over the patterned dielectric structure, on the first ferroelectric portion, and along the surface of the second recess, and removing an excess of the gate dielectric layer such that a portion of the gate dielectric layer is left on the surface of the second recess to serve as the gate dielectric.
2. The method of claim 1, wherein the memory gate and the logic gate are formed simultaneously.
3. The method of claim 2, wherein the formation of the memory gate and the logic gate includes: depositing a metal fill layer to fill the first recess and the second recess; and removing an excess of the metal fill layer such that the metal fill layer is formed into the memory gate in the first recess and the logic gate in the second recess.
4. The method of claim 3, wherein removing the excess of the gate dielectric layer, removing the excess of the first ferroelectric portion, and removing the excess of the metal fill layer are implemented simultaneously.
5. The method of claim 1, further comprising forming a P metal portion between the gate dielectric and the logic gate.
6. A method for manufacturing an integrated circuit, comprising: forming a memory well and a logic well in a semiconductor substrate, the memory well and the logic well being spaced apart from each other; forming two memory source/drain regions in the memory well so as to obtain a memory channel region between the two memory source/drain regions; forming two logic source/drain regions in the logic well so as to obtain a logic channel region between the two logic source/drain regions; forming a patterned dielectric structure on the semiconductor substrate, the patterned dielectric structure having a first recess which exposes the memory channel region, and a second recess which exposes the logic channel region; forming a ferroelectric layer over the patterned dielectric structure such that the ferroelectric layer is formed along inner surfaces of the first recess and inner surfaces of the second recess; removing a portion of the ferroelectric layer on the inner surfaces of the second recess; forming a gate dielectric layer over the patterned dielectric structure such that the gate dielectric layer is formed on a remaining portion of the ferroelectric

layer and is formed along the inner surfaces of the second recess; removing a portion of the gate dielectric layer on the remaining portion of the ferroelectric layer; forming a p metal layer over the patterned dielectric structure such that the p metal layer is formed to cover the remaining portion of the ferroelectric layer and a remaining portion of the gate dielectric layer; patterning the p metal layer into a p metal portion which is disposed on the remaining portion of the gate dielectric layer in the second recess; forming a metal filling layer to fill the first recess and the second recess and to cover the remaining portion of the ferroelectric layer, the remaining portion of the gate dielectric layer, and the p metal portion; and performing a planarization process to planarize the remaining portion of the ferroelectric layer, the remaining portion of the gate dielectric layer, and the metal filling layer, such that the remaining portion of the ferroelectric layer is formed into a data storage element on the inner surfaces of the first recess, the remaining portion of the gate dielectric layer is formed into a gate dielectric on the inner surfaces of the second recess, and the metal filling layer is formed into a first metal portion and a second metal portion which are respectively in the first recess and the second recess.

7. The method of claim 6, wherein the patterned dielectric structure is formed by: forming a dummy memory structure on the memory well before formation of the two memory source/drain regions such that the memory channel region is disposed beneath the dummy memory structure; forming two memory gate spacers at two opposite sides of the dummy memory structure; forming a dummy logic structure on the logic well before formation of the two logic source/drain regions such that the logic channel region is disposed beneath the dummy logic structure; forming two logic gate spacers at two opposite sides of the dummy logic structure; removing the dummy memory structure after formation of the two memory source/drain regions so as to form the first recess located between the two memory gate spacers and on the memory channel region; and removing the dummy logic structure after formation of the two logic source/drain regions so as to form the second recess located between the two logic gate spacers and on the logic channel region.

8. The method of claim 7, wherein: formation of the two memory gate spacers includes forming two first sidewall spacers at the two opposite sides of the dummy memory structure, and forming two second sidewall spacers respectively on the two first sidewall spacers; and after formation of the two memory gate spacers, the two memory source/drain regions are formed in two opposite regions of the memory well which are exposed from the two memory gate spacers and the dummy memory structure.

9. The method of claim 8, further comprising: before formation of the two second sidewall spacers, forming two lightly doped regions in the two opposite regions of the memory well which are exposed from the two first sidewall spacers and the dummy memory structure such that after formation of the two memory source/drain regions, each of the two memory source/drain regions partially overlaps a corresponding one of the two lightly doped regions, the two lightly doped regions having a doping concentration lower than that of the two memory source/drain regions.

10. The method of claim 6, wherein the ferroelectric layer has a thickness ranging from 50 Å to 150 Å.

11. The method of claim 6, wherein the gate dielectric layer has a thickness ranging from 5 Å to 30 Å.

12. The method of claim 6, wherein the ferroelectric layer includes hafnium oxide, hafnium silicate, hafnium zirconate, barium titanate, lead titanate, strontium titanate, calcium manganite, bismuth ferrite, aluminum scandium nitride, aluminum gallium nitride, aluminum yttrium nitride, doped hafnium oxide, lead zirconate titanate, barium strontium titanate, strontium bismuth tantalate, or combinations thereof.

13. The method of claim 6, wherein each of the data storage element and the gate dielectric has a U-shape cross section.

14. A method for manufacturing an integrated circuit, comprising: forming a memory well and a logic well respectively in a memory substrate region and a logic substrate region of a

semiconductor substrate, the memory well having two memory source/drain regions and a memory channel region between the two memory source/drain regions, the logic well having two logic source/drain regions and a logic channel region between the two logic source/drain regions; forming a patterned dielectric structure on the semiconductor substrate, the patterned dielectric structure having a first recess which exposes the memory channel region, and a second recess which exposes the logic channel region; forming a data storage element along a surface of the first recess; forming a gate dielectric along a surface of the second recess; forming a memory gate in the first recess such that the data storage element is disposed around the memory gate; and forming a logic gate in the second recess such that the gate dielectric is disposed around the logic gate, wherein the formation of the data storage element includes: conformally depositing a ferroelectric layer over the patterned dielectric structure along the surface of the first recess and along the surface of the second recess, partially removing the ferroelectric layer such that a first ferroelectric portion of the ferroelectric layer is left on the memory substrate region, and removing an excess of the first ferroelectric portion such that a region of the first ferroelectric portion is left on the surface of the first recess to serve as the data storage element; wherein the formation of the gate dielectric includes: conformally depositing a gate dielectric layer over the patterned dielectric structure, on the first ferroelectric portion, and along the surface of the second recess, and removing an excess of the gate dielectric layer such that a portion of the gate dielectric layer is left on the surface of the second recess to serve as the gate dielectric; and wherein the ferroelectric layer has a thickness ranging from 50 Å to 150 Å.

15. The method of claim 14, wherein the gate dielectric layer has a thickness ranging from 5 Å to 30 Å.

16. The method of claim 14, wherein the memory gate and the logic gate are formed simultaneously.

17. The method of claim 16, wherein the formation of the memory gate and the logic gate includes: depositing a metal fill layer on the gate dielectric layer to fill the first recess and the second recess; and removing an excess of the metal fill layer such that the metal fill layer is formed into the memory gate in the first recess and the logic gate in the second recess.

18. The method of claim 17, wherein removing the excess of the gate dielectric layer, removing the excess of the first ferroelectric portion, and removing the excess of the metal fill layer are implemented simultaneously.

19. The method of claim 14, further comprising forming a P metal portion between the gate dielectric and the logic gate.

20. The method of claim 14, wherein each of the data storage element and the gate dielectric has a U-shape cross section.
