

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408925
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Vu; John et al.

Multiple layer devices for treatment of vascular defects

Abstract

Devices and methods for treatment of a patient's vasculature are described. Embodiments may include a first permeable shell and a second permeable shell, where the second permeable shell sits within an interior cavity of the first permeable shell. The first and second permeable shells may each be made from a plurality of elongate filaments that are woven together to form a mesh. The mesh of the first permeable shell may have a larger mesh density and be softer than the mesh of the second permeable shell.

Inventors: Vu; John (Santa Ana, CA), Luu; Nathan (Garden Grove, CA), Hewitt; Todd (Laguna Niguel, CA), Tran; Hung P. (Midway City, CA)

Applicant: MICROVENTION, INC. (Aliso Viejo, CA)

Family ID: 77664075

Assignee: MICROVENTION, INC. (Aliso Viejo, CA)

Appl. No.: 18/221559

Filed: July 13, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230363763 A1	Nov. 16, 2023

Related U.S. Application Data

continuation parent-doc US 17197197 20210310 ABANDONED child-doc US 18221559
us-provisional-application US 62988173 20200311

Publication Classification

Int. Cl.: A61B17/12 (20060101); A61B17/00 (20060101); A61B90/00 (20160101)

U.S. Cl.:

CPC A61B17/12172 (20130101); A61B17/12113 (20130101); A61B2017/1205 (20130101); A61B2090/3966 (20160201)

Field of Classification Search

CPC: A61B (17/12172); A61B (17/12177); A61B (17/12122); A61B (90/39)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3874388	12/1974	King et al.	N/A	N/A
4282875	12/1980	Serbinnenko	N/A	N/A
4346712	12/1981	Handa et al.	N/A	N/A
4402319	12/1982	Handa et al.	N/A	N/A
4619246	12/1985	Molgaard-Nielsen et al.	N/A	N/A
4675361	12/1986	Ward	N/A	N/A
4729278	12/1987	Graeff	N/A	N/A
4998539	12/1990	Delsanti	N/A	N/A
5061275	12/1990	Wallsten et al.	N/A	N/A
5071407	12/1990	Termin et al.	N/A	N/A
5108407	12/1991	Geremia et al.	N/A	N/A
5122136	12/1991	Gluglielmi et al.	N/A	N/A
5154705	12/1991	Fleischhacker et al.	N/A	N/A
5158545	12/1991	Trudell et al.	N/A	N/A
5165421	12/1991	Fleischhacker et al.	N/A	N/A
5263963	12/1992	Garrison	N/A	N/A
5334210	12/1993	Gianturco	N/A	N/A
5378239	12/1994	Termin	N/A	N/A
5536247	12/1995	Thornton	N/A	N/A
5562725	12/1995	Schmitt et al.	N/A	N/A
5569245	12/1995	Gluglielmi et al.	N/A	N/A
5578074	12/1995	Mirigian	N/A	N/A
5591222	12/1996	Susawa et al.	N/A	N/A
5601595	12/1996	Smith	N/A	N/A
5630840	12/1996	Mayer	N/A	N/A
D380266	12/1996	Boatman et al.	N/A	N/A
5645559	12/1996	Hachtman et al.	N/A	N/A
5725552	12/1997	Kotula	N/A	N/A
5725570	12/1997	Heath	N/A	N/A
5733294	12/1997	Forber	N/A	N/A
5749883	12/1997	Halpern	N/A	N/A
5759161	12/1997	Ogawa	N/A	N/A
5766219	12/1997	Horton	N/A	N/A

5846261	12/1997	Kotula et al.	N/A	N/A
5873907	12/1998	Frantzen	N/A	N/A
5907893	12/1998	Zadno-Azizi	N/A	N/A
5916235	12/1998	Guglielmi	N/A	N/A
5925060	12/1998	Forber	N/A	N/A
5927345	12/1998	Samson	N/A	N/A
5928260	12/1998	Chin et al.	N/A	N/A
5935148	12/1998	Villar et al.	N/A	N/A
5944733	12/1998	Engelson	N/A	N/A
5944738	12/1998	Amplatz	N/A	N/A
5951599	12/1998	McCrory	N/A	N/A
5964797	12/1998	Ho	N/A	N/A
5980554	12/1998	Lenker et al.	N/A	N/A
5984929	12/1998	Bashiri et al.	N/A	N/A
5989242	12/1998	Saadat et al.	N/A	N/A
6033423	12/1999	Ken et al.	N/A	N/A
6063070	12/1999	Eder	N/A	N/A
6063104	12/1999	Villar et al.	N/A	N/A
6086577	12/1999	Ken et al.	N/A	N/A
6093199	12/1999	Brown et al.	N/A	N/A
6123715	12/1999	Amplatz	N/A	N/A
6139564	12/1999	Teoh et al.	N/A	N/A
6142975	12/1999	Jalisi et al.	N/A	N/A
6152144	12/1999	Lesh et al.	N/A	N/A
6156061	12/1999	Wallace et al.	N/A	N/A
6159206	12/1999	Ogawa	N/A	N/A
6168615	12/2000	Ken et al.	N/A	N/A
6168618	12/2000	Frantzen	N/A	N/A
6168622	12/2000	Mazzocchi	N/A	N/A
6190402	12/2000	Horton et al.	N/A	N/A
6193708	12/2000	Ken et al.	N/A	N/A
6203779	12/2000	Ricci et al.	N/A	N/A
6221086	12/2000	Forber	N/A	N/A
6238403	12/2000	Greene, Jr. et al.	N/A	N/A
6277126	12/2000	Barry et al.	N/A	N/A
6290721	12/2000	Heath	N/A	N/A
6315709	12/2000	Garibaldi et al.	N/A	N/A
6325815	12/2000	Kusleika	N/A	N/A
6342068	12/2001	Thompson	N/A	N/A
6344048	12/2001	Chin et al.	N/A	N/A
6346117	12/2001	Greenhalgh	N/A	N/A
6350270	12/2001	Roue	N/A	N/A
6368338	12/2001	Konya	N/A	N/A
6368339	12/2001	Amplatz	N/A	N/A
6375668	12/2001	Gifford	N/A	N/A
6375670	12/2001	Greenhalgh	N/A	N/A
6383174	12/2001	Eder	N/A	N/A
6391037	12/2001	Greenhalgh	N/A	N/A
6425914	12/2001	Wallace et al.	N/A	N/A
6428558	12/2001	Jones et al.	N/A	N/A

6447531	12/2001	Amplatz	N/A	N/A
6454780	12/2001	Wallace	N/A	N/A
6461370	12/2001	Gray et al.	N/A	N/A
6463317	12/2001	Kucharczyk	N/A	N/A
6468266	12/2001	Bashiri et al.	N/A	N/A
6478773	12/2001	Gandhi et al.	N/A	N/A
6500149	12/2001	Gandhi et al.	N/A	N/A
6506204	12/2002	Mazzocchi	N/A	N/A
6511468	12/2002	Cragg et al.	N/A	N/A
6551303	12/2002	Van Tassel et al.	N/A	N/A
6579303	12/2002	Amplatz	N/A	N/A
6585748	12/2002	Jeffree	N/A	N/A
6589256	12/2002	Forber	N/A	N/A
6589265	12/2002	Palmer et al.	N/A	N/A
6599308	12/2002	Amplatz	N/A	N/A
6605102	12/2002	Mazzocchi et al.	N/A	N/A
6605111	12/2002	Bose et al.	N/A	N/A
6607539	12/2002	Hayashi et al.	N/A	N/A
6613074	12/2002	Mitelberg	N/A	N/A
6626939	12/2002	Burnside et al.	N/A	N/A
6632241	12/2002	Hancock	N/A	N/A
6635068	12/2002	Dubrul et al.	N/A	N/A
6638257	12/2002	Amplatz	N/A	N/A
6652556	12/2002	Van Tassel et al.	N/A	N/A
6666882	12/2002	Bose et al.	N/A	N/A
6669721	12/2002	Bose et al.	N/A	N/A
6682546	12/2003	Amplatz	N/A	N/A
6689150	12/2003	Van Tassel et al.	N/A	N/A
6689486	12/2003	Ho et al.	N/A	N/A
6719778	12/2003	Van Tassel et al.	N/A	N/A
6730119	12/2003	Smalling	N/A	N/A
6743236	12/2003	Barry et al.	N/A	N/A
6743251	12/2003	Eder	N/A	N/A
6746468	12/2003	Sepetka et al.	N/A	N/A
6746890	12/2003	Gupta et al.	N/A	N/A
6752826	12/2003	Holloway et al.	N/A	N/A
6780196	12/2003	Chin et al.	N/A	N/A
6811560	12/2003	Jones et al.	N/A	N/A
6818006	12/2003	Douk et al.	N/A	N/A
6855153	12/2004	Saadat	N/A	N/A
6855154	12/2004	Abdel-Gawwad	N/A	N/A
6878384	12/2004	Cruise et al.	N/A	N/A
6936055	12/2004	Ken et al.	N/A	N/A
6940209	12/2004	Henderson	N/A	N/A
6953472	12/2004	Palmer et al.	N/A	N/A
6953473	12/2004	Porter	N/A	N/A
6966892	12/2004	Gandhi et al.	N/A	N/A
6994092	12/2005	van der Burg et al.	N/A	N/A
7001409	12/2005	Amplatz	N/A	N/A
7004962	12/2005	Stinson	N/A	N/A

7011671	12/2005	Welch	N/A	N/A
7044958	12/2005	Douk et al.	N/A	N/A
7052513	12/2005	Thompson	N/A	N/A
7083632	12/2005	Avellanet et al.	N/A	N/A
7101390	12/2005	Nelson	N/A	N/A
7122043	12/2005	Greenhalgh et al.	N/A	N/A
7128736	12/2005	Abrams et al.	N/A	N/A
7179276	12/2006	Barry et al.	N/A	N/A
7182774	12/2006	Barry et al.	N/A	N/A
7195636	12/2006	Avellanet et al.	N/A	N/A
7198613	12/2006	Gandhi et al.	N/A	N/A
7201918	12/2006	Cruise	N/A	N/A
7229454	12/2006	Tran	N/A	N/A
7229461	12/2006	Chin et al.	N/A	N/A
7275471	12/2006	Nishri et al.	N/A	N/A
7326225	12/2007	Ferrera et al.	N/A	N/A
7329279	12/2007	Haug et al.	N/A	N/A
7331980	12/2007	Dubrul	N/A	N/A
7410482	12/2007	Murphy	N/A	N/A
7419503	12/2007	Pulnev et al.	N/A	N/A
7490396	12/2008	Bradley	N/A	N/A
7524319	12/2008	Dubrul	N/A	N/A
7569066	12/2008	Gerberding	N/A	N/A
7573382	12/2008	Choubey et al.	N/A	N/A
7575582	12/2008	Gandhi et al.	N/A	N/A
7578826	12/2008	Gandhi et al.	N/A	N/A
7597704	12/2008	Frazier et al.	N/A	N/A
7648532	12/2009	Greenhalgh et al.	N/A	N/A
7695488	12/2009	Berenstein	N/A	N/A
7722637	12/2009	Barry et al.	N/A	N/A
7745732	12/2009	Michael et al.	N/A	N/A
7806919	12/2009	Bloom et al.	N/A	N/A
7862577	12/2010	Gray et al.	N/A	N/A
7942925	12/2010	Yodaf	N/A	N/A
7989703	12/2010	Schaffer	N/A	N/A
8043326	12/2010	Hancock	N/A	N/A
8043329	12/2010	Khairkhahan	N/A	N/A
8066757	12/2010	Ferrera et al.	N/A	N/A
8142456	12/2011	Rosqueta et al.	N/A	N/A
8182506	12/2011	Fitz et al.	N/A	N/A
8192480	12/2011	Tieu et al.	N/A	N/A
8261648	12/2011	Marchand et al.	N/A	N/A
8313505	12/2011	Amplatz et al.	N/A	N/A
8398670	12/2012	Amplatz	N/A	N/A
8430012	12/2012	Marchand	N/A	N/A
8506619	12/2012	Ortiz et al.	N/A	N/A
8551132	12/2012	Eskridge et al.	N/A	N/A
8597320	12/2012	Sepetka	N/A	N/A
8597323	12/2012	Plaza et al.	N/A	N/A
8690907	12/2013	Janardhan et al.	N/A	N/A

8715338	12/2013	Frid	N/A	N/A
8728117	12/2013	Janardhan et al.	N/A	N/A
8747430	12/2013	Porter	N/A	N/A
8758395	12/2013	Kleshinski et al.	N/A	N/A
8795330	12/2013	Janardhan et al.	N/A	N/A
8826791	12/2013	Thompson et al.	N/A	N/A
8840735	12/2013	Schaffer	N/A	N/A
8845679	12/2013	Janardhan et al.	N/A	N/A
9078658	12/2014	Hewitt et al.	N/A	N/A
9161758	12/2014	Figulla et al.	N/A	N/A
9198668	12/2014	Theobald et al.	N/A	N/A
9198670	12/2014	Hewitt et al.	N/A	N/A
9259337	12/2015	Cox et al.	N/A	N/A
9272323	12/2015	Schaffer	N/A	N/A
9295473	12/2015	Hewitt et al.	N/A	N/A
9351715	12/2015	Mach	N/A	N/A
9492174	12/2015	Hewitt et al.	N/A	N/A
9504588	12/2015	Sadisivan et al.	N/A	N/A
9585669	12/2016	Becking et al.	N/A	N/A
9597087	12/2016	Marchand et al.	N/A	N/A
9629635	12/2016	Hewitt et al.	N/A	N/A
9687245	12/2016	Molaei et al.	N/A	N/A
9855047	12/2017	Berez et al.	N/A	N/A
9955976	12/2017	Hewitt et al.	N/A	N/A
10123803	12/2017	Ferrera et al.	N/A	N/A
10130372	12/2017	Griffin	N/A	N/A
10136896	12/2017	Hewitt et al.	N/A	N/A
10238393	12/2018	Marchand et al.	N/A	N/A
10260182	12/2018	Thompson et al.	N/A	N/A
10260183	12/2018	Marchand et al.	N/A	N/A
10398441	12/2018	Warner et al.	N/A	N/A
10426589	12/2018	Van der Burg et al.	N/A	N/A
10470773	12/2018	Maguire et al.	N/A	N/A
10617426	12/2019	Aboytes et al.	N/A	N/A
10716573	12/2019	Connor	N/A	N/A
10736758	12/2019	Ruvalcaba et al.	N/A	N/A
10813645	12/2019	Hewitt et al.	N/A	N/A
10856880	12/2019	Badrudin et al.	N/A	N/A
10939914	12/2020	Hewitt et al.	N/A	N/A
10952739	12/2020	Plaza et al.	N/A	N/A
11033277	12/2020	Wolfe et al.	N/A	N/A
11058431	12/2020	Pereira et al.	N/A	N/A
11185335	12/2020	Badrudin et al.	N/A	N/A
11202636	12/2020	Zaidat et al.	N/A	N/A
11284901	12/2021	Griffin	N/A	N/A
11317921	12/2021	Hewitt et al.	N/A	N/A
11389174	12/2021	Griffin	N/A	N/A
11464518	12/2021	Connor	N/A	N/A
11559309	12/2022	Rangwala et al.	N/A	N/A
11723667	12/2022	Hewitt et al.	N/A	N/A

11786253	12/2022	Divino et al.	N/A	N/A
2001/0031981	12/2000	Evans et al.	N/A	N/A
2002/0065552	12/2001	Jayaraman et al.	N/A	N/A
2002/0103542	12/2001	Bilbo	N/A	N/A
2002/0111647	12/2001	Khairkhahan et al.	N/A	N/A
2002/0143349	12/2001	Gifford, III et al.	N/A	N/A
2002/0143361	12/2001	Douk et al.	N/A	N/A
2002/0156499	12/2001	Konya et al.	N/A	N/A
2002/0169473	12/2001	Sepetka et al.	N/A	N/A
2002/0183787	12/2001	Wahr et al.	N/A	N/A
2002/0187288	12/2001	Lim et al.	N/A	N/A
2003/0012816	12/2002	West et al.	N/A	N/A
2003/0028209	12/2002	Teoh et al.	N/A	N/A
2003/0040771	12/2002	Hyodoh et al.	N/A	N/A
2003/0167068	12/2002	Amplatz	N/A	N/A
2003/0171739	12/2002	Murphy et al.	N/A	N/A
2003/0171774	12/2002	Freudenthal et al.	N/A	N/A
2003/0181942	12/2002	Sutton et al.	N/A	N/A
2003/0187473	12/2002	Berenstein et al.	N/A	N/A
2003/0199913	12/2002	Dubrul et al.	N/A	N/A
2004/0059370	12/2003	Green, Jr. et al.	N/A	N/A
2004/0098027	12/2003	Tech et al.	N/A	N/A
2004/0111147	12/2003	Rabkin et al.	N/A	N/A
2004/0122367	12/2003	Sculati et al.	N/A	N/A
2004/0143239	12/2003	Zhou et al.	N/A	N/A
2004/0158311	12/2003	Berhow	N/A	N/A
2004/0172053	12/2003	Barry et al.	N/A	N/A
2004/0186562	12/2003	Cox	N/A	N/A
2004/0193206	12/2003	Gerberding et al.	N/A	N/A
2004/0193208	12/2003	Talpade et al.	N/A	N/A
2004/0220563	12/2003	Eder	N/A	N/A
2004/0260333	12/2003	Dubrul et al.	N/A	N/A
2005/0021075	12/2004	Bonnette et al.	N/A	N/A
2005/0033408	12/2004	Jones et al.	N/A	N/A
2005/0053782	12/2004	Sen et al.	N/A	N/A
2005/0096728	12/2004	Ramer	N/A	N/A
2005/0112349	12/2004	Laurencin et al.	N/A	N/A
2005/0113861	12/2004	Corcoran et al.	N/A	N/A
2005/0113868	12/2004	Devellian et al.	N/A	N/A
2005/0119684	12/2004	Guttermann et al.	N/A	N/A
2005/0133046	12/2004	Becker et al.	N/A	N/A
2005/0137623	12/2004	Jones et al.	N/A	N/A
2005/0149173	12/2004	Hunter et al.	N/A	N/A
2005/0216052	12/2004	Mazzocchi et al.	N/A	N/A
2005/0222489	12/2004	Rahdert et al.	N/A	N/A
2005/0228422	12/2004	Machold et al.	N/A	N/A
2005/0228434	12/2004	Amplatz et al.	N/A	N/A
2005/0267516	12/2004	Soleimani et al.	N/A	N/A
2005/0277978	12/2004	Greenhalgh	N/A	N/A
2006/0009798	12/2005	Callister et al.	N/A	N/A

2006/0009799	12/2005	Kleshinski et al.	N/A	N/A
2006/0009800	12/2005	Christianson et al.	N/A	N/A
2006/0052815	12/2005	Fitz et al.	N/A	N/A
2006/0052816	12/2005	Bates et al.	N/A	N/A
2006/0064151	12/2005	Guterman et al.	N/A	N/A
2006/0083721	12/2005	Cohen et al.	N/A	N/A
2006/0106421	12/2005	Teoh	N/A	N/A
2006/0116708	12/2005	Ogawa et al.	N/A	N/A
2006/0135947	12/2005	Soltesz et al.	N/A	N/A
2006/0155323	12/2005	Porter et al.	N/A	N/A
2006/0178694	12/2005	Greenhalgh et al.	N/A	N/A
2006/0200192	12/2005	Fitz et al.	N/A	N/A
2006/0200234	12/2005	Hines	N/A	N/A
2006/0212055	12/2005	Karabey et al.	N/A	N/A
2006/0217799	12/2005	Mailander et al.	N/A	N/A
2006/0235464	12/2005	Avellanet et al.	N/A	N/A
2006/0241690	12/2005	Amplatz et al.	N/A	N/A
2006/0247680	12/2005	Amplatz et al.	N/A	N/A
2006/0252984	12/2005	Rahdert et al.	N/A	N/A
2006/0253149	12/2005	Gandhi et al.	N/A	N/A
2006/0271086	12/2005	Ramzipoor et al.	N/A	N/A
2007/0021816	12/2006	Rudin	N/A	N/A
2007/0031584	12/2006	Roth	N/A	N/A
2007/0061006	12/2006	Desatnik et al.	N/A	N/A
2007/0088387	12/2006	Eskridge et al.	N/A	N/A
2007/0100419	12/2006	Licata et al.	N/A	N/A
2007/0106311	12/2006	Wallace et al.	N/A	N/A
2007/0106323	12/2006	Barry et al.	N/A	N/A
2007/0112380	12/2006	Figulla et al.	N/A	N/A
2007/0142906	12/2006	Figulla et al.	N/A	N/A
2007/0144124	12/2006	Schewe et al.	N/A	N/A
2007/0167911	12/2006	Gandhi et al.	N/A	N/A
2007/0167980	12/2006	Figulla et al.	N/A	N/A
2007/0173928	12/2006	Morsi	N/A	N/A
2007/0203062	12/2006	Ellis-Behnke et al.	N/A	N/A
2007/0208373	12/2006	Zaver et al.	N/A	N/A
2007/0208376	12/2006	Meng	N/A	N/A
2007/0225760	12/2006	Moszner et al.	N/A	N/A
2007/0233186	12/2006	Meng	N/A	N/A
2007/0255388	12/2006	Rudakov et al.	N/A	N/A
2007/0265656	12/2006	Amplatz et al.	N/A	N/A
2007/0288083	12/2006	Hines	N/A	N/A
2007/0299464	12/2006	Cruise et al.	N/A	N/A
2008/0033341	12/2007	Grad	N/A	N/A
2008/0033366	12/2007	Matson	N/A	N/A
2008/0033475	12/2007	Meng	N/A	N/A
2008/0033478	12/2007	Meng	N/A	N/A
2008/0097495	12/2007	Feller, III et al.	N/A	N/A
2008/0119886	12/2007	Greenhalgh et al.	N/A	N/A
2008/0161936	12/2007	Feller et al.	N/A	N/A

2008/0188923	12/2007	Chu	N/A	N/A
2008/0195139	12/2007	Donald et al.	N/A	N/A
2008/0200945	12/2007	Amplatz et al.	N/A	N/A
2008/0221600	12/2007	Dieck et al.	N/A	N/A
2008/0228215	12/2007	Strauss et al.	N/A	N/A
2008/0281350	12/2007	Sepetka et al.	N/A	N/A
2009/0025820	12/2008	Adams	N/A	N/A
2009/0062812	12/2008	Fitz et al.	N/A	N/A
2009/0062834	12/2008	Moftakhar	N/A	N/A
2009/0062841	12/2008	Amplatz et al.	N/A	N/A
2009/0082803	12/2008	Adams et al.	N/A	N/A
2009/0099647	12/2008	Glimsdale et al.	N/A	N/A
2009/0112305	12/2008	Goldmann et al.	N/A	N/A
2009/0132024	12/2008	Berkhoff	N/A	N/A
2009/0163780	12/2008	Tieu	N/A	N/A
2009/0227976	12/2008	Calabria	N/A	N/A
2009/0275974	12/2008	Marchand	N/A	N/A
2009/0287291	12/2008	Becking et al.	N/A	N/A
2009/0287294	12/2008	Rosqueta et al.	N/A	N/A
2009/0318948	12/2008	Linder et al.	N/A	N/A
2010/0004679	12/2009	Osyka	N/A	N/A
2010/0023048	12/2009	Mach	N/A	N/A
2010/0023105	12/2009	Levy et al.	N/A	N/A
2010/0069948	12/2009	Veznedaroglu et al.	N/A	N/A
2010/0094409	12/2009	Barker et al.	N/A	N/A
2010/0106235	12/2009	Kariniemi et al.	N/A	N/A
2010/0262182	12/2009	Moszner et al.	N/A	N/A
2011/0022149	12/2010	Cox	N/A	N/A
2011/0029008	12/2010	Gesswein	N/A	N/A
2011/0046658	12/2010	Connor et al.	N/A	N/A
2011/0046719	12/2010	Frid	N/A	N/A
2011/0054515	12/2010	Bridgeman	N/A	N/A
2011/0082493	12/2010	Samson et al.	N/A	N/A
2011/0144669	12/2010	Becking et al.	N/A	N/A
2011/0152823	12/2010	Mohiuddin et al.	N/A	N/A
2011/0152993	12/2010	Marchand et al.	N/A	N/A
2011/0202085	12/2010	Loganathan et al.	N/A	N/A
2011/0208227	12/2010	Becking	N/A	N/A
2011/0208233	12/2010	McGuckin	N/A	N/A
2011/0224776	12/2010	Sepekta et al.	N/A	N/A
2011/0295298	12/2010	Moszner	N/A	N/A
2011/0319926	12/2010	Becking	N/A	N/A
2012/0065667	12/2011	Javois et al.	N/A	N/A
2012/0143237	12/2011	Cam	N/A	N/A
2012/0165919	12/2011	Cox et al.	N/A	N/A
2012/0197283	12/2011	Marchand et al.	N/A	N/A
2012/0271337	12/2011	Figulla et al.	N/A	N/A
2012/0283768	12/2011	Cox et al.	N/A	N/A
2012/0330341	12/2011	Becking et al.	N/A	N/A
2013/0066357	12/2012	Aboytes et al.	N/A	N/A

2013/0092012	12/2012	Marchand et al.	N/A	N/A
2013/0092013	12/2012	Thompson et al.	N/A	N/A
2013/0116722	12/2012	Aboytes et al.	N/A	N/A
2013/0123830	12/2012	Becking et al.	N/A	N/A
2013/0211495	12/2012	Halden et al.	N/A	N/A
2013/0233160	12/2012	Marchand et al.	N/A	N/A
2013/0239790	12/2012	Thompson et al.	N/A	N/A
2013/0245667	12/2012	Marchand et al.	N/A	N/A
2013/0268053	12/2012	Molaei et al.	N/A	N/A
2013/0274862	12/2012	Cox et al.	N/A	N/A
2013/0274863	12/2012	Cox et al.	N/A	N/A
2013/0274866	12/2012	Cox et al.	N/A	N/A
2013/0274868	12/2012	Cox et al.	N/A	N/A
2013/0296912	12/2012	Ottma	N/A	N/A
2013/0325051	12/2012	Martin et al.	N/A	N/A
2014/0005713	12/2013	Bowman et al.	N/A	N/A
2014/0005714	12/2013	Quick et al.	N/A	N/A
2014/0018841	12/2013	Peiffer et al.	N/A	N/A
2014/0052233	12/2013	Cox et al.	N/A	N/A
2014/0058436	12/2013	Rosenbluth et al.	N/A	N/A
2014/0074151	12/2013	Tischler et al.	N/A	N/A
2014/0135734	12/2013	Dakin et al.	N/A	N/A
2014/0135817	12/2013	Tischler et al.	N/A	N/A
2014/0135827	12/2013	Amplatz et al.	N/A	N/A
2014/0142611	12/2013	Plaza et al.	N/A	N/A
2014/0172001	12/2013	Becking et al.	N/A	N/A
2014/0200607	12/2013	Sepetka et al.	N/A	N/A
2014/0257360	12/2013	Keillor	N/A	N/A
2014/0257361	12/2013	Prom	N/A	N/A
2014/0318354	12/2013	Thompson et al.	N/A	N/A
2014/0318355	12/2013	Marchand et al.	N/A	N/A
2014/0330299	12/2013	Rosenbluth et al.	N/A	N/A
2014/0358178	12/2013	Hewitt et al.	N/A	N/A
2015/0012033	12/2014	Plaza et al.	N/A	N/A
2015/0133989	12/2014	Lubock et al.	N/A	N/A
2015/0182674	12/2014	Schaffer	N/A	N/A
2015/0272589	12/2014	Lorenzo	N/A	N/A
2015/0283363	12/2014	Hewitt et al.	N/A	N/A
2015/0313605	12/2014	Griffin	N/A	N/A
2015/0374483	12/2014	Janardhan et al.	N/A	N/A
2016/0015396	12/2015	Cox et al.	N/A	N/A
2016/0015398	12/2015	Hewitt et al.	N/A	N/A
2016/0030052	12/2015	Cragg et al.	N/A	N/A
2016/0045201	12/2015	Rosenbluth et al.	N/A	N/A
2016/0100842	12/2015	Plaza et al.	N/A	N/A
2016/0192941	12/2015	Hewitt et al.	N/A	N/A
2016/0249934	12/2015	Hewitt et al.	N/A	N/A
2016/0249935	12/2015	Hewitt et al.	N/A	N/A
2016/0249937	12/2015	Marchand et al.	N/A	N/A
2016/0262769	12/2015	Cragg et al.	N/A	N/A

2016/0324528	12/2015	Hebert et al.	N/A	N/A
2016/0324668	12/2015	Wallace et al.	N/A	N/A
2016/0335757	12/2015	Florent et al.	N/A	N/A
2016/0367260	12/2015	Hewitt et al.	N/A	N/A
2017/0035437	12/2016	Sarge et al.	N/A	N/A
2017/0079662	12/2016	Rhee et al.	N/A	N/A
2017/0088988	12/2016	Thompson et al.	N/A	N/A
2017/0095254	12/2016	Hewitt et al.	N/A	N/A
2017/0128077	12/2016	Hewitt et al.	N/A	N/A
2017/0191195	12/2016	Marchand et al.	N/A	N/A
2017/0224350	12/2016	Shimizu et al.	N/A	N/A
2017/0245862	12/2016	Cox et al.	N/A	N/A
2017/0258473	12/2016	Plaza et al.	N/A	N/A
2018/0000489	12/2017	Marchand et al.	N/A	N/A
2018/0070955	12/2017	Greene, Jr. et al.	N/A	N/A
2018/0140305	12/2017	Connor	N/A	N/A
2018/0153554	12/2017	Walzman	N/A	N/A
2018/0185130	12/2017	Janardhan et al.	N/A	N/A
2018/0206849	12/2017	Hewitt et al.	N/A	N/A
2018/0206851	12/2017	Walzman	N/A	N/A
2018/0271540	12/2017	Merritt et al.	N/A	N/A
2018/0303486	12/2017	Rosenbluth et al.	N/A	N/A
2018/0338767	12/2017	Dasnurkar et al.	N/A	N/A
2019/0046209	12/2018	Plaza et al.	N/A	N/A
2019/0059909	12/2018	Griffin	N/A	N/A
2019/0192166	12/2018	Hewitt et al.	N/A	N/A
2019/0192167	12/2018	Lorenzo	N/A	N/A
2019/0209180	12/2018	Kealey et al.	N/A	N/A
2019/0218696	12/2018	Thompson et al.	N/A	N/A
2019/0223876	12/2018	Badruddin et al.	N/A	N/A
2019/0223881	12/2018	Hewitt et al.	N/A	N/A
2019/0269414	12/2018	Griffin	N/A	N/A
2019/0290286	12/2018	Divino et al.	N/A	N/A
2019/0298364	12/2018	Walsh et al.	N/A	N/A
2019/0343533	12/2018	Costalat	N/A	N/A
2019/0365385	12/2018	Gorochow et al.	N/A	N/A
2020/0038035	12/2019	Griffin	N/A	N/A
2020/0113576	12/2019	Gorochow et al.	N/A	N/A
2020/0289124	12/2019	Rangwala et al.	N/A	N/A
2020/0289125	12/2019	Dholakia et al.	N/A	N/A
2020/0289126	12/2019	Hewitt et al.	N/A	N/A
2020/0367894	12/2019	Pereira et al.	N/A	N/A
2020/0367898	12/2019	Gorochow et al.	N/A	N/A
2021/0007754	12/2020	Milhous et al.	N/A	N/A
2021/0085333	12/2020	Gorochow et al.	N/A	N/A
2021/0128165	12/2020	Pulugurtha et al.	N/A	N/A
2021/0153871	12/2020	Griffin	N/A	N/A
2021/0212698	12/2020	Connor	N/A	N/A
2021/0236279	12/2020	Yohanan et al.	N/A	N/A
2021/0275184	12/2020	Hewitt et al.	N/A	N/A

2022/0192678	12/2021	Hewitt et al.	N/A	N/A
2022/0257260	12/2021	Hewitt et al.	N/A	N/A
2022/0323084	12/2021	Griffin	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2009242528	12/2015	AU	N/A
2722037	12/2008	CA	N/A
106974691	12/2016	CN	N/A
0706876	12/1999	EP	N/A
0808138	12/2004	EP	N/A
1576929	12/2004	EP	N/A
1844717	12/2006	EP	N/A
1923019	12/2007	EP	N/A
2055263	12/2008	EP	N/A
2258275	12/2010	EP	N/A
2596754	12/2012	EP	N/A
2157937	12/2016	EP	N/A
2333169	12/1996	FR	N/A
52141092	12/1976	JP	N/A
H4-47415	12/1991	JP	N/A
WO 95/30384	12/1994	WO	N/A
WO 96/01591	12/1995	WO	N/A
WO 97/26939	12/1996	WO	N/A
WO 99/03404	12/1998	WO	N/A
WO 99/05977	12/1998	WO	N/A
WO 99/62432	12/1998	WO	N/A
WO 01/45571	12/2000	WO	N/A
WO 01/93782	12/2000	WO	N/A
WO 02/00139	12/2001	WO	N/A
WO 03/011151	12/2002	WO	N/A
WO 03/032818	12/2002	WO	N/A
WO 03/063732	12/2002	WO	N/A
WO 2004/047649	12/2003	WO	N/A
WO 2004/093742	12/2003	WO	N/A
WO 2005/117718	12/2004	WO	N/A
WO 2006/026744	12/2005	WO	N/A
WO 2006/055683	12/2005	WO	N/A
WO 2007/006139	12/2006	WO	N/A
WO 2007/096183	12/2006	WO	N/A
WO 2008/151204	12/2007	WO	N/A
WO 2009/036219	12/2008	WO	N/A
WO 2009/048700	12/2008	WO	N/A
WO 2009/121006	12/2008	WO	N/A
WO 2009/126747	12/2008	WO	N/A
WO 2009/132045	12/2008	WO	N/A
WO 2009/134337	12/2008	WO	N/A
WO 2009/135166	12/2008	WO	N/A
WO 2010/134914	12/2009	WO	N/A
WO 2011/057002	12/2010	WO	N/A

WO 2013/102848	12/2012	WO	N/A
WO 2013/119332	12/2012	WO	N/A
WO 2014/087245	12/2013	WO	N/A
WO 2014/169261	12/2013	WO	N/A
WO 2015/160721	12/2014	WO	N/A
WO 2015/171268	12/2014	WO	N/A
WO 2015/192019	12/2014	WO	N/A
WO 2017/153603	12/2016	WO	N/A
WO 2018/051187	12/2017	WO	N/A
WO 2018/058033	12/2017	WO	N/A
WO 2019/040494	12/2018	WO	N/A
WO 2021/183793	12/2020	WO	N/A

OTHER PUBLICATIONS

A Complete Microcatheter Portfolio; A Broad Selection of Microcatheters. Boston Scientific Brochure 2007. cited by applicant

Allen et al., "Micromachine Wedge Stepping Motor," pp. 1-6, Nov. 12-20, 1998. ASME International Mechanical Engineering Congress, Anaheim, CA. cited by applicant

Altes et al., "Creation of Saccular Aneurysms in the Rabbit: A model Suitable for Testing Endovascular Devices," American Roentgen Ray Society, Feb. 2000. cited by applicant

Ansari et al., "Thrombosis of a Fusiform Intracranial Aneurysm Induced by Overlapping Neuroform Stents: Case Report," *Neurosurgery*, E950-E951 vol. 60, No. 5, May 2007. cited by applicant

Atritech Press Release, Minneapolis, Jun. 18, 2007 "Atritech Announces Intellectual Property Acquisition, Transaction Establishes Company as leader in Left Atrial Appendage Market." cited by applicant

Caroff, J. et al., "Woven Endobridge (WEB) Device for endovascular treatment of ruptured intracranial wide-neck aneurysms: a single-center experience," *Neuroradiology*, 56(9):755-761 (Sep. 2014). cited by applicant

Caroff, J. et al., "Role of C-Arm VasoCT in the Use of Endovascular WEB Flow Disruption in Intracranial Aneurysm Treatment," *AJNR Am. J. Neuroradiol.* 35(7):1353- 1357 (Jul. 2014). cited by applicant

Colla, R. et al., "Treatment of Wide-Neck Basilar Tip Aneurysms Using the Web II Device," *The Neuroradiology Journal* 26(6):669-677 (Dec. 2013). cited by applicant

De Backer, O. et al., "Percutaneous left atrial appendage occlusion for stroke prevention in atrial fibrillation: an update," *Open Heart*, 4:1-14 (2013). cited by applicant

Ding, Y.H. et al., "The Woven EndoBridge: A New Aneurysm Occlusion Device," *AJNR Am. J. Neuroradiol.* 32:607-611 (Mar. 2011). cited by applicant

Duerig, T.W., "The Use of Superelasticity in Modern Medicine," *MRS Bulletin*, pp. 101-104 (Feb. 2002). cited by applicant

Fiorella, D. et al., "Interobserver variability in the assessment of aneurysm occlusion with the WEB aneurysm embolization system," *J. NeuroIntervent. Surg.* Jul. 1, 2014, pii: neurintsurg-2014-011251. doi: 10.1136/neurintsurg-2014-011251 [Epub ahead of print]. cited by applicant

Fort Wayne Metals HHS Tube brochure, p. 28-29 (2009), Fort Wayne, Indiana, www.oldsite.fwmetals.com. cited by applicant

Grabenwoger et al., "Endothelialization of Biosynthetic vascular Prosthesis After Laser Perforation," *Ann Thorac Surg*, 66:S110-S114 (1998). cited by applicant

Guider Softip XF Guide Catheters Brochure, Boston Scientific Corporation 2004. cited by applicant

Gupta et al., "Nitinol Thin Film Three Dimensional Devices-Fabrication and Applications," From:

SMST-2003: Proceedings of the International Conference on Shape Memory and Superelastic Technologies Published: 2004. cited by applicant

Hill et al., "Initial Results of the Amplatzer® Vascular Plug in the treatment of Congenital Heart Disease," Technology and Services, *Business Briefing: US Cardiology*, pp. 1-3 (2004). cited by applicant

Jeffree et al., "The Porus, Guidewire-Directed, Detachable Aneurysm Liner: A New Concept in the Endovascular Treatment of Intracranial Aneurysms," *AJNR Am J Neuradiol* 20:774-779 (May 1999). cited by applicant

Kallmes et al., "A New Endoluminal, Flow-Disrupting Device for Treatment of Saccular Aneurysms," *Stroke*, Journal of the American Heart Association 38:1-7 (2007). cited by applicant

Klisch, J. et al., "The Woven EndoBridge Cerebral Aneurysm Embolization Device (WEB II): initial clinical experience," *Neuroradiology* 53:599-607 (2011). cited by applicant

Kónya, A. et al., "Preliminary Results with a New Vascular Basket Occluder in Swine," *JVIR*, 10(8):1043-1049 (1999). cited by applicant

Kwon et al., "Preliminary Results of the Luna Aneurysm Embolization System in a Rabbit Model: A New Intracapsular Aneurysm Occlusion Device," *AJNR Am J Neuroradiol*, 32:602-606 (Mar. 2011). cited by applicant

Lendlein, A. et al., "Shape-Memory Polymers," *Angew. Chem. Int. Ed.*, 41:2034-2057 (2002). cited by applicant

Lendlein, A. et al., "Biodegradable, Elastic Shape-Memory Polymers for Potential Biomedical Applications," *Science* 296:1673-1676 (May 31, 2002). cited by applicant

Lieber, B.B. et al., "The Role of Blood Impulse in Cerebral Aneurysm Coil Compaction: Effect of Aneurysm Neck Size," IMECE2003-43099, Proceedings of IMECE '03, 2003 ASME International Mechanical Engineering Congress, Washington, D.C. (Nov. 15-21, 2003). cited by applicant

Liu, C. et al., "Review of progress in shape-memory polymers," *J. Mater. Chem.* 17:1543-1558 (2007). cited by applicant

Lubicz, B. et al., "WEB Device for Endovascular Treatment of Wide-Neck Bifurcation Aneurysms," *AJNR Am. J. Neuroradiol.* 34(6):1209-1214 (Jun.-Jul. 2013). cited by applicant

Lubicz, B. et al., "WEB-DL Endovascular Treatment of Wide-Neck Bifurcation Aneurysms: Short- and Midterm Results in a European Study," *AJNR Am. J. Neuroradiol.* 35(3):432-438 (Mar. 2014). doi: 10.3174/ajnr.A3869. Epub Jan. 23, 2014. cited by applicant

Major, S. et al., "Life of Nitinol Drawn Filed Wires with Ag or Au Core for Medical Application," *International Journal of Mechanics* 2(7):73-80 (2013). cited by applicant

Matinlinna et al., "An Introduction to Silanes and Their Clinical Applications in Dentistry," *The International Journal of Prosthodontics*, 17(2):155-164 (2004). cited by applicant

Mine et al., "Intracapsular flow-diversion for treatment of intracranial aneurysms: the Woven EndoBridge," *Expert Rev. Med. Devices* 11(3): 315-325 (May 2014). doi: 10.1586/17434440.2014.907741. Epub Apr. 2, 2014. cited by applicant

Nakayama et al., "Development of Microporous Covered Stents: Geometrical Design of the Luminal Surface," *The International Journal of Artificial Organs*, 28(6):600-608 (2005). cited by applicant

Nemat-Nasser, S. et al., "Superelastic and cyclic response of NiTi SMA at various strain rates and temperatures," *Mechanics of Materials* 38:463-474 (2006). cited by applicant

Nishi et al., "Embolization of experimental aneurysms using a heparin-loaded stent graft with micropores," *Cardiovascular Radiation Medicine* 4:29-33 (2003). cited by applicant

Nishi et al., "Occlusion of Experimental Aneurysms with Heparin-Loaded, Microporous Stent Grafts," *Neurosurgery* 53(6):1397-1405 (Dec. 2003). cited by applicant

Papagiannaki, C. et al., "WEB Intracapsular Flow Disruptor—Prospective, Multicenter Experience in 83 Patients with 85 Aneurysms," *AJNR Am. J. Neuroradiol.* 35(11):2106-2111 (Nov.-Dec. 2014). 35(11):2106-11. doi: 10.3174/ajnr.A4028. Epub Jul. 3, 2014. cited by applicant

Park, J. et al., "Percutaneous Left Atrial Appendage Transcatheter Occlusion (PLAATO) for Stroke Prevention in Atrial Fibrillation: 2-Year Outcome," *J Invasive. Cardiol.*, 21(9):446-450 (2009). cited by applicant

Pelton, A.R. et al., "Optimisation of processing and properties of medical grade Nitinol wire," *Min. Invas. Ther. & Allied Technol.* 9(1):107-118 (2000). cited by applicant

Pham, Q. et al., "Electrospinning of Polymeric Nanofibers for Tissue Engineering Applications: A Review," *Tissue Engr* 12(5):1197-1211 (1996). cited by applicant

Pierot, L. et al., "Intrasaccular Flow-Disruption Treatment of Intracranial Aneurysms: Preliminary Results of a Multicenter Clinical Study," *AJNR Am J Neuroradiol.* 33(7):1232-1238 (Aug. 2012). doi: 10.3174/ajnr.A3191. Epub Jun. 7, 2012. cited by applicant

Pierot, L. et al., "Endovascular WEB Flow Disruption in Middle Cerebral Artery Aneurysms: Preliminary Feasibility, Clinical, and Anatomical Results in a Multicenter Study," *Neurosurgery* 73(1):27-35 (Jul. 2013). cited by applicant

Pierot, L. et al., "Role, safety, and efficacy of WEB flow disruption: a review," *EJMINT* Invited Review, 2014: 1419000139 (May 8, 2014). cited by applicant

Peirot, L. et al., "WEB Treatment of Intracranial Aneurysms: Feasiblity, Complications, and 1-Month Safety Results with the WEB DL and WEB SL/SLS in the French Observatory," *AJNR Am J Neuroradiol.* Feb. 5, 2015 [Epub ahead ofprint]. cited by applicant

Romero, J. et al., "Left Atrial Appendage Closure Devices," *Clinical Medicine Insights: Cardiology*, 8:45-52 (2014). cited by applicant

Rottiers, W. et al., "Shape Memory Materials and their applications," in Korolev's readings: conference proceedings, pp. 250-250 (2011). cited by applicant

Salamat et al., "Experimental Evaluation of a New Transcatheter Vascular Embolization Device in the Swine Model," *J Vasc Interv Radiol*, 12:301-311 (2002). cited by applicant

Schaffer, J.E. et al., "Engineering Characteristics of Drawn Filled Nitinol Tube," SMST-2003: Proceedings of the International Conference on Shape Memory and Superelastic Technologies (ASM International), pp. 109-118 (2004). cited by applicant

Schmitz-Rode, T. et al., "Self-expandable spindle for transcatheter vascular occlusion: in vivo experiments. Work in progress." *Radiology* 188:95-100 (Jul. 1993). cited by applicant

Simgen, A. et al., "Evaluation of a newly designed flow diverter for the treatment of intracranial aneurysms in an elastase-induced aneurysm model, in New Zealand white rabbits," *Neuroradiology* 56:129-137 (2014). cited by applicant

Spelle, L. et al., "Letter to the Editor," *Neuroradiol J.* Jun. 2014; 27(3):369. doi: 10.15274/NRJ-2014-10048. Epub Jun. 17, 2014. cited by applicant

Stoeckel, D. et al., "Self-expanding nitinol stents: material and design considerations," *Eur. Radiol.* 14:292-301 (2004). cited by applicant

Turk, A. et al., "Evaluation of the TriSpan Neck Bridge Device for the Treatment of Wide-Necked Aneurysms: An Experimental Study in Canines, Editorial Comment: An Experimental Study in Canines," *Stroke* 32:492-497 (Feb. 2001). cited by applicant

Wallner, A.K. et al., "Coiling after Treatment with the Woven EndoBridge Cerebral Aneurysm Embolization Device," *Interventional Neuroradiology* 18:208-212 (2012). cited by applicant

Yeow, W.L. et al., Device- and LAA-Specific Characteristics for Successful LAA Closures: Tips and Tricks, *Intervent. Cardiol. Clin.*, 3:239-254 (2014). cited by applicant

Zimmermann et al., "Patent Foramen Oval Closure With the SeptRx Device, Initial Experience with the First "In-Tunnel" Device," *JACC Cardiovascular Interventions* vol. 3, No. 9., 2010. cited by applicant

International Search Report and Written Opinion mailed Oct. 31, 2008 for International Application No. PCT/US2008/065694. cited by applicant

International Search Report and Written Opinion mailed Nov. 26, 2009 for International Application No. PCT/US2009/042592. cited by applicant

International Search Report and Written Opinion mailed Jul. 28, 2011 for International Application No. PCT/US2010/055494. cited by applicant
International Search Report and Written Opinion mailed Jul. 21, 2015 for International Application No. PCT/US2015/025609. cited by applicant
International Search Report and Written Opinion mailed Jan. 11, 2016 for International Application No. PCT/US2015/025613. cited by applicant
International Search Report and Written Opinion mailed Jun. 10, 2020 for International Application No. PCT/US2020/022275. cited by applicant
International Search Report and Written Opinion mailed Jun. 11, 2020 for International Application No. PCT/US2020/022364. cited by applicant
International Search Report and Written Opinion mailed Jun. 15, 2020 for International Application No. PCT/US2020/022319. cited by applicant
International Search Report and Written Opinion mailed Jul. 24, 2020 for International Application No. PCT/US2020/022096. cited by applicant
Extended European Search Report dated Apr. 24, 2014, in EP Appl No. EP 08770070 filed Jun. 3, 2008. cited by applicant
Extended European Search Report dated Jul. 30, 2014, in EP Appl No. EP 10829110 filed Nov. 4, 2010. cited by applicant
Extended European Search Report dated Dec. 13, 2017, in EP Appl No. EP 15789225.8 filed Jun. 5, 2015. cited by applicant
Official Action dated Mar. 8, 2019, in JP Appl. No. 2016-562549 filed Jun. 5, 2015. cited by applicant
Spelle, L. et al., "CLinical Assessment of WEB device in Ruptured aneurYSms (CLARYS): 12-month angiographic results of a multicenter study", J NeuroIntervent Surg, 2022, 0:1-6. cited by applicant
International Search Report and Written Opinion mailed Feb. 28, 2023 for International Application No. PCT/US2022/048938. cited by applicant
International Search Report and Written Opinion mailed Jul. 18, 2023, for International Application No. PCT/US2023/20560. cited by applicant
Final Official Action dated Mar. 12, 2024, in JP Appl. No. 2022-169903. cited by applicant

Primary Examiner: Nguyen; Tuan V

Attorney, Agent or Firm: ONE LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. application Ser. No. 17/197,197, filed Mar. 10, 2021, which claims the benefit of priority under 35 U.S.C. § 119(e) from U.S. Provisional Application Ser. No. 62/988,173, filed Mar. 11, 2020, both of which are hereby expressly incorporated by reference in their entireties for all purposes.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT
(1) Not applicable.

FIELD OF THE INVENTION

(2) Embodiments of devices and methods herein are directed to blocking a flow of fluid through a tubular vessel or into a small interior chamber of a saccular cavity or vascular defect within a mammalian body. More specifically, embodiments herein are directed to devices and methods for

treatment of a vascular defect of a patient including some embodiments directed specifically to the treatment of cerebral aneurysms of patients.

BACKGROUND

(3) The mammalian circulatory system is comprised of a heart, which acts as a pump, and a system of blood vessels which transport the blood to various points in the body. Due to the force exerted by the flowing blood on the blood vessel the blood vessels may develop a variety of vascular defects. One common vascular defect known as an aneurysm results from the abnormal widening of the blood vessel. Typically, vascular aneurysms are formed as a result of the weakening of the wall of a blood vessel and subsequent ballooning and expansion of the vessel wall. If, for example, an aneurysm is present within an artery of the brain, and the aneurysm should burst with resulting cranial hemorrhaging, death could occur.

(4) Surgical techniques for the treatment of cerebral aneurysms typically involve a craniotomy requiring creation of an opening in the skull of the patient through which the surgeon can insert instruments to operate directly on the patient's brain. For some surgical approaches, the brain must be retracted to expose the parent blood vessel from which the aneurysm arises. Once access to the aneurysm is gained, the surgeon places a clip across the neck of the aneurysm thereby preventing arterial blood from entering the aneurysm. Upon correct placement of the clip the aneurysm will be obliterated in a matter of minutes. Surgical techniques may be effective treatment for many aneurysms. Unfortunately, surgical techniques for treating these types of conditions include major invasive surgical procedures which often require extended periods of time under anesthesia involving high risk to the patient. Such procedures thus require that the patient be in generally good physical condition in order to be a candidate for such procedures.

(5) Various alternative and less invasive procedures have been used to treat cerebral aneurysms without resorting to major surgery. One approach to treating aneurysms without the need for invasive surgery involves the placement of sleeves or stents into the vessel and across the region where the aneurysm occurs. Such devices maintain blood flow through the vessel while reducing blood pressure applied to the interior of the aneurysm. Certain types of stents are expanded to the proper size by inflating a balloon catheter, referred to as balloon expandable stents, while other stents are designed to elastically expand in a self-expanding manner. Some stents are covered typically with a sleeve of polymeric material called a graft to form a stent-graft. Stents and stent-grafts are generally delivered to a preselected position adjacent a vascular defect through a delivery catheter. In the treatment of cerebral aneurysms, covered stents or stent-grafts have seen very limited use due to the likelihood of inadvertent occlusion of small perforator vessels that may be near the vascular defect being treated.

(6) In addition, current uncovered stents are generally not sufficient as a stand-alone treatment. In order for stents to fit through the microcatheters used in small cerebral blood vessels, their density is usually reduced such that when expanded there is only a small amount of stent structure bridging the aneurysm neck. Thus, they do not block enough flow to cause clotting of the blood in the aneurysm and are thus generally used in combination with vaso-occlusive devices, such as the coils discussed above, to achieve aneurysm occlusion.

(7) Some procedures involve the delivery of embolic or filling materials into an aneurysm. The delivery of such vaso-occlusion devices or materials may be used to promote hemostasis or fill an aneurysm cavity entirely. Vaso-occlusion devices may be placed within the vasculature of the human body, typically via a catheter, either to block the flow of blood through a vessel with an aneurysm through the formation of an embolus or to form such an embolus within an aneurysm stemming from the vessel. A variety of implantable, coil-type vaso-occlusion devices are known. The coils of such devices may themselves be formed into a secondary coil shape, or any of a variety of more complex secondary shapes. Vaso-occlusive coils are commonly used to treat cerebral aneurysms but suffer from several limitations including poor packing density, compaction due to hydrodynamic pressure from blood flow, poor stability in wide-necked aneurysms, and

complexity and difficulty in the deployment thereof as most aneurysm treatments with this approach require the deployment of multiple coils. Coiling is less effective at treating certain physiological conditions, such as wide neck cavities (e.g. wide neck aneurysms) because there is a greater risk of the coils migrating out of the treatment site. Because there is a risk of the coils falling out of the aneurysm, a balloon or stent is typically also used along the neck of the aneurysm to provide a scaffold and help keep the coils within the target region—though even with these devices there is still a risk of the coils sticking out of the aneurysm.

(8) A number of aneurysm neck bridging devices with defect spanning portions or regions have been attempted, however, none of these devices have had a significant measure of clinical success or usage. A major limitation in their adoption and clinical usefulness is the inability to position the defect spanning portion to assure coverage of the neck. Existing stent delivery systems that are neurovascular compatible (i.e. deliverable through a microcatheter and highly flexible) do not have the necessary rotational positioning capability. Another limitation of many aneurysm bridging devices described in the prior art is the poor flexibility. Cerebral blood vessels are tortuous, and a high degree of flexibility is required for effective delivery to most aneurysm locations in the brain.

(9) What has been needed are devices and methods for delivery and use in small and tortuous blood vessels that can substantially block the flow of blood into an aneurysm, such as a cerebral aneurysm, with a decreased risk of inadvertent aneurysm rupture or blood vessel wall damage. In addition, what has been needed are methods and devices suitable for blocking blood flow in cerebral aneurysms over an extended period of time without a significant risk of deformation, compaction or dislocation.

(10) Alternative occlusive approaches to fill an aneurysm can utilize more conformable structures that conform to the shape of the treatment site. Sometimes these occlusive structures are singular devices that are implanted into the aneurysm. Sometimes these occlusive devices can be considered as intrasaccular devices that conform to the shape of the treatment site and also provide enhanced disruption to blood flow at the neck region of the aneurysm.

(11) Intrasaccular occlusive devices are part of a newer type of occlusion device used to treat various intravascular conditions including aneurysms. They are often more effective at treating these wide neck conditions, or larger treatment areas. The intrasaccular devices comprise a structure that sits within the aneurysm and provides an occlusive effect at the neck of the aneurysm to help limit blood flow into the aneurysm. The rest of the device comprises a relatively conformable structure that sits within the aneurysm helping to occlude all or a portion of the aneurysm. Intrasaccular devices typically conform to the shape of the treatment site. These devices also occlude the cross section of the neck of the treatment site/aneurysm, thereby promoting clotting and causing thrombosis and closing of the aneurysm over time.

(12) Although the distal tip of intrasaccular devices rarely cause procedural complications, some physicians perceive the distal end of intrasaccular devices to be rigid during initial deployment and are concerned that the distal marker band can act as a “point contact” for force against the aneurysm wall until the implant starts to “flower open,” at which point any force is applied across a much larger surface area.

(13) The following embodiments address these issues utilizing concepts that minimize pressure applied to the dome of an aneurysm.

SUMMARY

(14) An occlusive device is described that is used to treat a variety of conditions, including aneurysms and neurovascular aneurysms. In some embodiments, the occlusion device is configured as an intrasaccular device.

(15) In many embodiments, an intrasaccular implant includes an inner and an outer layer, each layer being made from a plurality of filaments woven into a mesh. The outer layer may be softer (e.g., less stiff) than the inner layer. Thus, the outer layer may be made from filaments that have a smaller diameter than the filaments used to make the inner layer. The inner layer may be stiffer

than the outer layer and serve as a structural layer, which helps to deploy the softer outer layer fully into its desired shape. The inner layer may be made from a smaller number of filaments having a larger diameter as compared to the filaments forming the outer layer. The braid angle of the outer layer may be much higher than the braid angle of the inner layer. The mismatch of the braid angles of the inner and outer layer may help ensure that a substantial length of the softer outer layer deploys before the inner, structural layer exits the delivery device. This may also mitigate the risk of interference between the distal marker bands of the inner and outer layers by creating space between the layers during deployment and recapture.

(16) In many embodiments, a device for treatment of a patient's cerebral aneurysm includes first and second permeable shells. Each of the first and second permeable shells have a proximal end, a distal end, a radially constrained elongated state configured for delivery within a catheter lumen, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a plurality of elongate filaments that are woven together to form a mesh. The expanded state of the first permeable shell defines an interior cavity and the second permeable shell sits within the interior cavity of the first permeable shell. In some embodiments, the first and second permeable shells each have an average mesh density, and wherein the average mesh density of the second permeable shell is smaller than the average mesh density of the first permeable shell. In some embodiments, the first and second permeable shells each have an average pore size, and wherein the average pore size of the second permeable shell is larger than the average pore size of the first permeable shell.

(17) In many embodiments, a method for treating a cerebral aneurysm having an interior cavity and a neck includes the steps of advancing an implant in a microcatheter to a region of interest in a cerebral artery, deploying the implant within the cerebral aneurysm, and withdrawing the microcatheter from the region of interest after deploying the implant. The implant includes first and second permeable shells. Each of the first and second permeable shells have a proximal end, a distal end, a radially constrained elongated state configured for delivery within a catheter lumen, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a plurality of elongate filaments that are woven together to form a mesh. The expanded state of the first permeable shell defines an interior cavity and the second permeable shell sits within the interior cavity of the first permeable shell. The first and second permeable shells expand to each of their expanded states in the interior cavity of the aneurysm. In some embodiments, the first and second permeable shells each have an average mesh density, and wherein the average mesh density of the second permeable shell is smaller than the average mesh density of the first permeable shell. In some embodiments, the first and second permeable shells each have an average pore size, and wherein the average pore size of the second permeable shell is larger than the average pore size of the first permeable shell.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is an elevation view of an embodiment of a device for treatment of a patient's vasculature and a plurality of arrows indicating inward radial force.

(2) FIG. 2 is an elevation view of a beam supported by two simple supports and a plurality of arrows indicating force against the beam.

(3) FIG. 3 is a bottom perspective view of an embodiment of a device for treatment of a patient's vasculature.

(4) FIG. 4 is an elevation view of the device for treatment of a patient's vasculature of FIG. 3.

(5) FIG. 5 is a transverse cross sectional view of the device of FIG. 4 taken along lines 5-5 in FIG.

- (6) FIG. 6 shows the device of FIG. 4 in longitudinal section taken along lines 6-6 in FIG. 4.
- (7) FIG. 7 is an enlarged view of the woven filament structure taken from the encircled portion 7 shown in FIG. 5.
- (8) FIG. 8 is an enlarged view of the woven filament structure taken from the encircled portion 8 shown in FIG. 6.
- (9) FIG. 9 is a proximal end view of the device of FIG. 3.
- (10) FIG. 10 is a transverse sectional view of a proximal hub portion of the device in FIG. 6 indicated by lines 10-10 in FIG. 6.
- (11) FIG. 11 is an elevation view in partial section of a distal end of a delivery catheter with the device for treatment of a patient's vasculature of FIG. 3 disposed therein in a collapsed constrained state.
- (12) FIG. 12 illustrates an embodiment of a filament configuration for a device for treatment of a patient's vasculature.
- (13) FIG. 13 shows an embodiment of a device for treatment of an aneurysm having multiple layers.
- (14) FIGS. 14-15 show the device of FIG. 13 as it is deployed from a delivery catheter.
- (15) FIG. 16 shows the device of FIG. 13 deployed in an aneurysm.
- (16) FIG. 17 is a schematic view of a patient being accessed by an introducer sheath, a microcatheter and a device for treatment of a patient's vasculature releasably secured to a distal end of a delivery device or actuator.
- (17) FIG. 18 is a sectional view of a terminal aneurysm.
- (18) FIG. 19 is a sectional view of an aneurysm.
- (19) FIG. 20 is a schematic view in section of an aneurysm showing perpendicular arrows which indicate interior nominal longitudinal and transverse dimensions of the aneurysm.
- (20) FIG. 21 is a schematic view in section of the aneurysm of FIG. 20 with a dashed outline of a device for treatment of a patient's vasculature in a relaxed unconstrained state that extends transversely outside of the walls of the aneurysm.
- (21) FIG. 22 is a schematic view in section of an outline of a device represented by the dashed line in FIG. 21 in a deployed and partially constrained state within the aneurysm.
- (22) FIGS. 23-26 show a deployment sequence of a device for treatment of a patient's vasculature.
- (23) FIG. 27 is an elevation view in partial section of an embodiment of a device for treatment of a patient's vasculature deployed within an aneurysm at a tilted angle.
- (24) FIG. 28 is an elevation view in partial section of an embodiment of a device for treatment of a patient's vasculature deployed within an irregularly shaped aneurysm.
- (25) FIG. 29 shows an elevation view in section of a device for treatment of a patient's vasculature deployed within a vascular defect aneurysm.

DETAILED DESCRIPTION

(26) Discussed herein are devices and methods for the treatment of vascular defects that are suitable for minimally invasive deployment within a patient's vasculature, and particularly, within the cerebral vasculature of a patient. For such embodiments to be safely and effectively delivered to a desired treatment site and effectively deployed, some device embodiments may be configured for collapse to a low profile constrained state with a transverse dimension suitable for delivery through an inner lumen of a microcatheter and deployment from a distal end thereof. Embodiments of these devices may also maintain a clinically effective configuration with sufficient mechanical integrity once deployed so as to withstand dynamic forces within a patient's vasculature over time that may otherwise result in compaction of a deployed device. It may also be desirable for some device embodiments to acutely occlude a vascular defect of a patient during the course of a procedure in order to provide more immediate feedback regarding success of the treatment to a treating physician.

(27) Intracascular occlusive devices that include a permeable shell formed from a woven or braided

mesh have been described in US 2017/0095254, US 2016/0249934, US 2016/0367260, US 2016/0249937, and US 2018/0000489, all of which are hereby expressly incorporated by reference in their entirety for all purposes.

(28) Some embodiments are particularly useful for the treatment of cerebral aneurysms by reconstructing a vascular wall so as to wholly or partially isolate a vascular defect from a patient's blood flow. Some embodiments may be configured to be deployed within a vascular defect to facilitate reconstruction, bridging of a vessel wall or both in order to treat the vascular defect. For some of these embodiments, the permeable shell of the device may be configured to anchor or fix the permeable shell in a clinically beneficial position. For some embodiments, the device may be disposed in whole or in part within the vascular defect in order to anchor or fix the device with respect to the vascular structure or defect. The permeable shell may be configured to span an opening, neck or other portion of a vascular defect in order to isolate the vascular defect, or a portion thereof, from the patient's nominal vascular system in order allow the defect to heal or to otherwise minimize the risk of the defect to the patient's health.

(29) For some or all of the embodiments of devices for treatment of a patient's vasculature discussed herein, the permeable shell may be configured to allow some initial perfusion of blood through the permeable shell. The porosity of the permeable shell may be configured to sufficiently isolate the vascular defect so as to promote healing and isolation of the defect, but allow sufficient initial flow through the permeable shell so as to reduce or otherwise minimize the mechanical force exerted on the membrane the dynamic flow of blood or other fluids within the vasculature against the device. For some embodiments of devices for treatment of a patient's vasculature, only a portion of the permeable shell that spans the opening or neck of the vascular defect, sometimes referred to as a defect spanning portion, need be permeable and/or conducive to thrombus formation in a patient's bloodstream. For such embodiments, that portion of the device that does not span an opening or neck of the vascular defect may be substantially non-permeable or completely permeable with a pore or opening configuration that is too large to effectively promote thrombus formation.

(30) In general, it may be desirable in some cases to use a hollow, thin walled device with a permeable shell of resilient material that may be constrained to a low profile for delivery within a patient. Such a device may also be configured to expand radially outward upon removal of the constraint such that the shell of the device assumes a larger volume and fills or otherwise occludes a vascular defect within which it is deployed. The outward radial expansion of the shell may serve to engage some or all of an inner surface of the vascular defect whereby mechanical friction between an outer surface of the permeable shell of the device and the inside surface of the vascular defect effectively anchors the device within the vascular defect. Some embodiments of such a device may also be partially or wholly mechanically captured within a cavity of a vascular defect, particularly where the defect has a narrow neck portion with a larger interior volume. In order to achieve a low profile and volume for delivery and be capable of a high ratio of expansion by volume, some device embodiments include a matrix of woven or braided filaments that are coupled together by the interwoven structure so as to form a self-expanding permeable shell having a pore or opening pattern between couplings or intersections of the filaments that is substantially regularly spaced and stable, while still allowing for conformity and volumetric constraint.

(31) As used herein, the terms woven and braided are used interchangeably to mean any form of interlacing of filaments to form a mesh structure. In the textile and other industries, these terms may have different or more specific meanings depending on the product or application such as whether an article is made in a sheet or cylindrical form. For purposes of the present disclosure, these terms are used interchangeably.

(32) For some embodiments, three factors may be critical for a woven or braided wire occlusion device for treatment of a patient's vasculature that can achieve a desired clinical outcome in the endovascular treatment of cerebral aneurysms. We have found that for effective use in some

applications, it may be desirable for the implant device to have sufficient radial stiffness for stability, limited pore size for near-complete acute (intra-procedural) occlusion and a collapsed profile which is small enough to allow insertion through an inner lumen of a microcatheter. A device with a radial stiffness below a certain threshold may be unstable and may be at higher risk of embolization in some cases. Larger pores between filament intersections in a braided or woven structure may not generate thrombus and occlude a vascular defect in an acute setting and thus may not give a treating physician or health professional such clinical feedback that the flow disruption will lead to a complete and lasting occlusion of the vascular defect being treated. Delivery of a device for treatment of a patient's vasculature through a standard microcatheter may be highly desirable to allow access through the tortuous cerebral vasculature in the manner that a treating physician is accustomed. A detailed discussion of radial stiffness, pore size, and the necessary collapsed profile can be found in US 2017/0095254, which was previously expressly incorporated by reference in its entirety.

(33) As has been discussed, some embodiments of devices for treatment of a patient's vasculature call for sizing the device which approximates (or with some over-sizing) the vascular site dimensions to fill the vascular site. One might assume that scaling of a device to larger dimensions and using larger filaments would suffice for such larger embodiments of a device. However, for the treatment of brain aneurysms, the diameter or profile of the radially collapsed device is limited by the catheter sizes that can be effectively navigated within the small, tortuous vessels of the brain. Further, as a device is made larger with a given or fixed number of resilient filaments having a given size or thickness, the pores or openings between junctions of the filaments are correspondingly larger. In addition, for a given filament size the flexural modulus or stiffness of the filaments and thus the structure decrease with increasing device dimension. Flexural modulus may be defined as the ratio of stress to strain. Thus, a device may be considered to have a high flexural modulus or be stiff if the strain (deflection) is low under a given force. A stiff device may also be said to have low compliance.

(34) To properly configure larger size devices for treatment of a patient's vasculature, it may be useful to model the force on a device when the device is deployed into a vascular site or defect, such as a blood vessel or aneurysm, that has a diameter or transverse dimension that is smaller than a nominal diameter or transverse dimension of the device in a relaxed unconstrained state. As discussed, it may be advisable to "over-size" the device in some cases so that there is a residual force between an outside surface of the device and an inside surface of the vascular wall. The inward radial force on a device **10** that results from over-sizing is illustrated schematically in FIG. **1** with the arrows **12** in the figure representing the inward radial force. As shown in FIG. **2**, these compressive forces on the filaments **14** of the device in FIG. **1** can be modeled as a simply supported beam **16** with a distributed load or force as shown by the arrows **18** in the figure. It can be seen from the equation below for the deflection of a beam with two simple supports **20** and a distributed load that the deflection is a function of the length, L to the 4th power: Deflection of Beam = $\frac{5FL^4}{384EI}$ where F=force, L=length of beam, E=Young's Modulus, and I=moment of inertia.

(35) Thus, as the size of the device increases and L increases, the compliance increases substantially. Accordingly, an outward radial force exerted by an outside surface of the filaments **14** of the device **10** against a constraining force when inserted into a vascular site such as blood vessel or aneurysm is lower for a given amount of device compression or over-sizing. This force may be important in some applications to assure device stability and to reduce the risk of migration of the device and potential distal embolization.

(36) In some embodiments, a combination of small and large filament sizes may be utilized to make a device with a desired radial compliance and yet have a collapsed profile which is configured to fit through an inner lumen of commonly used microcatheters. A device fabricated with even a small number of relatively large filaments **14** can provide reduced radial compliance

(or increased stiffness) compared to a device made with all small filaments. Even a relatively small number of larger filaments may provide a substantial increase in bending stiffness due to change in the moment of Inertia that results from an increase in diameter without increasing the total cross sectional area of the filaments. The moment of inertia (I) of a round wire or filament may be defined by the equation:

$I = \pi d^4 / 64$ where d is the diameter of the wire or filament.

(37) Since the moment of inertia is a function of filament diameter to the fourth power, a small change in the diameter greatly increases the moment of inertia. Thus, small changes in filament size can have substantial impact on the deflection at a given load and thus the compliance of the device.

(38) Thus, the stiffness can be increased by a significant amount without a large increase in the cross sectional area of a collapsed profile of the device **10**. This may be particularly important as device embodiments are made larger to treat large aneurysms. While large cerebral aneurysms may be relatively rare, they present an important therapeutic challenge as some embolic devices currently available to physicians have relatively poor results compared to smaller aneurysms.

(39) As such, some embodiments of devices for treatment of a patient's vasculature may be formed using a combination of filaments **14** with a number of different diameters such as 2, 3, 4, 5 or more different diameters or transverse dimensions. In device embodiments where filaments with two different diameters are used, some larger filament embodiments may have a transverse dimension of about 0.001 inches to about 0.004 inches and some small filament embodiments may have a transverse dimension or diameter of about 0.0004 inches and about 0.0015 inches, more specifically, about 0.0004 inches to about 0.001 inches. The ratio of the number of large filaments to the number of small filaments may be between about 2 and 12 and may also be between about 4 and 8. In some embodiments, the difference in diameter or transverse dimension between the larger and smaller filaments may be less than about 0.004 inches, more specifically, less than about 0.0035 inches, and even more specifically, less than about 0.002 inches.

(40) As discussed above, device embodiments **10** for treatment of a patient's vasculature may include a plurality of wires, fibers, threads, tubes or other filamentary elements that form a structure that serves as a permeable shell. For some embodiments, a globular shape may be formed from such filaments by connecting or securing the ends of a tubular braided structure. For such embodiments, the density of a braided or woven structure may inherently increase at or near the ends where the wires or filaments **14** are brought together and decrease at or near a middle portion **30** disposed between a proximal end **32** and distal end **34** of the permeable shell **40**. For some embodiments, an end or any other suitable portion of a permeable shell **40** may be positioned in an opening or neck of a vascular defect such as an aneurysm for treatment. As such, a braided or woven filamentary device with a permeable shell may not require the addition of a separate defect spanning structure having properties different from that of a nominal portion of the permeable shell to achieve hemostasis and occlusion of the vascular defect. Such a filamentary device may be fabricated by braiding, weaving or other suitable filament fabrication techniques. Such device embodiments may be shape set into a variety of three-dimensional shapes such as discussed herein.

(41) Referring to FIGS. **3-10**, an embodiment of a device for treatment of a patient's vasculature **10** is shown. The device **10** includes a self-expanding resilient permeable shell **40** having a proximal end **32**, a distal end **34**, a longitudinal axis **46** and further comprising a plurality of elongate resilient filaments **14** including large filaments **48** and small filaments **50** of at least two different transverse dimensions as shown in more detail in FIGS. **5, 7, and 18**. The filaments **14** have a woven structure and are secured relative to each other at proximal ends **60** and distal ends **62** thereof. The permeable shell **40** of the device has a radially constrained elongated state configured for delivery within a microcatheter **61**, as shown in FIG. **11**, with the thin woven filaments **14** extending longitudinally from the proximal end **42** to the distal end **44** radially adjacent each other along a length of the filaments.

(42) As shown in FIGS. 3-6, the permeable shell **40** also has an expanded relaxed state with a globular and longitudinally shortened configuration relative to the radially constrained state. In the expanded state, the woven filaments **14** form the self-expanding resilient permeable shell **40** in a smooth path radially expanded from a longitudinal axis **46** of the device between the proximal end **32** and distal end **34**. The woven structure of the filaments **14** includes a plurality of openings **64** in the permeable shell **40** formed between the woven filaments. For some embodiments, the largest of said openings **64** may be configured to allow blood flow through the openings only at a velocity below a thrombotic threshold velocity. Thrombotic threshold velocity has been defined, at least by some, as the time-average velocity at which more than 50% of a vascular graft surface is covered by thrombus when deployed within a patient's vasculature. In the context of aneurysm occlusion, a slightly different threshold may be appropriate. Accordingly, the thrombotic threshold velocity as used herein shall include the velocity at which clotting occurs within or on a device, such as device **10**, deployed within a patient's vasculature such that blood flow into a vascular defect treated by the device is substantially blocked in less than about 1 hour or otherwise during the treatment procedure. The blockage of blood flow into the vascular defect may be indicated in some cases by minimal contrast agent entering the vascular defect after a sufficient amount of contrast agent has been injected into the patient's vasculature upstream of the implant site and visualized as it dissipates from that site. Such sustained blockage of flow within less than about 1 hour or during the duration of the implantation procedure may also be referred to as acute occlusion of the vascular defect.

(43) As such, once the device **10** is deployed, any blood flowing through the permeable shell may be slowed to a velocity below the thrombotic threshold velocity and thrombus will begin to form on and around the openings in the permeable shell **40**. Ultimately, this process may be configured to produce acute occlusion of the vascular defect within which the device **10** is deployed. For some embodiments, at least the distal end of the permeable shell **40** may have a reverse bend in an everted configuration such that the secured distal ends **62** of the filaments **14** are withdrawn axially within the nominal permeable shell structure or contour in the expanded state. For some embodiments, the proximal end of the permeable shell further includes a reverse bend in an everted configuration such that the secured proximal ends **60** of the filaments **14** are withdrawn axially within the nominal permeable shell structure **40** in the expanded state. As used herein, the term everted may include a structure that is everted, partially everted and/or recessed with a reverse bend as shown in the device embodiment of FIGS. 3-6. For such embodiments, the ends **60** and **62** of the filaments **14** of the permeable shell or hub structure disposed around the ends may be withdrawn within or below the globular shaped periphery of the permeable shell of the device.

(44) The elongate resilient filaments **14** of the permeable shell **40** may be secured relative to each other at proximal ends **60** and distal ends **62** thereof by one or more methods including welding, soldering, adhesive bonding, epoxy bonding or the like. In addition to the ends of the filaments being secured together, a distal hub **66** may also be secured to the distal ends **62** of the thin filaments **14** of the permeable shell **40** and a proximal hub **68** secured to the proximal ends **60** of the thin filaments **14** of the permeable shell **40**. The proximal hub **68** may include a cylindrical member that extends proximally beyond the proximal ends **60** of the thin filaments so as to form a cavity **70** within a proximal portion of the proximal hub **68**. The proximal cavity **70** may be used for holding adhesives such as epoxy, solder or any other suitable bonding agent for securing an elongate detachment tether **72** that may in turn be detachably secured to a delivery apparatus such as is shown in FIG. **11**.

(45) For some embodiments, the elongate resilient filaments **14** of the permeable shell **40** may have a transverse cross section that is substantially round in shape and be made from a superelastic material that may also be a shape memory metal. The shape memory metal of the filaments of the permeable shell **40** may be heat set in the globular configuration of the relaxed expanded state as shown in FIGS. 3-6. Suitable superelastic shape memory metals may include alloys such as NiTi

alloy and the like. The superelastic properties of such alloys may be useful in providing the resilient properties to the elongate filaments **14** so that they can be heat set in the globular form shown, fully constrained for delivery within an inner lumen of a microcatheter and then released to self expand back to substantially the original heat set shape of the globular configuration upon deployment within a patient's body.

(46) The device **10** may have an everted filamentary structure with a permeable shell **40** having a proximal end **32** and a distal end **34** in an expanded relaxed state. The permeable shell **40** has a substantially enclosed configuration for the embodiments shown. Some or all of the permeable shell **40** of the device **10** may be configured to substantially block or impede fluid flow or pressure into a vascular defect or otherwise isolate the vascular defect over some period of time after the device is deployed in an expanded state. The permeable shell **40** and device **10** generally also has a low profile, radially constrained state, as shown in FIG. **11**, with an elongated tubular or cylindrical configuration that includes the proximal end **32**, the distal end **34** and a longitudinal axis **46**. While in the radially constrained state, the elongate flexible filaments **14** of the permeable shell **40** may be disposed substantially parallel and in close lateral proximity to each other between the proximal end and distal end forming a substantially tubular or compressed cylindrical configuration.

(47) Proximal ends **60** of at least some of the filaments **14** of the permeable shell **40** may be secured to the proximal hub **68** and distal ends **62** of at least some of the filaments **14** of the permeable shell **40** are secured to the distal hub **66**, with the proximal hub **68** and distal hub **66** being disposed substantially concentric to the longitudinal axis **46** as shown in FIG. **4**. The ends of the filaments **14** may be secured to the respective hubs **66** and **68** by any of the methods discussed above with respect to securement of the filament ends to each other, including the use of adhesives, solder, welding and the like. A middle portion **30** of the permeable shell **40** may have a first transverse dimension with a low profile suitable for delivery from a microcatheter as shown in FIG. **11**. Radial constraint on the device **10** may be applied by an inside surface of the inner lumen of a microcatheter, such as the distal end portion of the microcatheter **61** shown, or it may be applied by any other suitable mechanism that may be released in a controllable manner upon ejection of the device **10** from the distal end of the catheter. In FIG. **11** a proximal end or hub **68** of the device **10** is secured to a distal end of an elongate delivery apparatus **111** of a delivery system **112** disposed at the proximal hub **68** of the device **10**. Additional details of delivery devices can be found in, e.g., US 2016/0367260, which was previously incorporated by reference in its entirety.

(48) Some device embodiments **10** having a braided or woven filamentary structure may be formed using about 10 filaments to about 300 filaments **14**, more specifically, about 10 filaments to about 100 filaments **14**, and even more specifically, about 60 filaments to about 80 filaments **14**. Some embodiments of a permeable shell **40** may include about 70 filaments to about 300 filaments extending from the proximal end **32** to the distal end **34**, more specifically, about 100 filaments to about 200 filaments extending from the proximal end **32** to the distal end **34**. For some embodiments, the filaments **14** may have a transverse dimension or diameter of about 0.0008 inches to about 0.004 inches. The elongate resilient filaments **14** in some cases may have an outer transverse dimension or diameter of about 0.0005 inch to about 0.005 inch, more specifically, about 0.001 inch to about 0.003 inch, and in some cases about 0.0004 inches to about 0.002 inches. For some device embodiments **10** that include filaments **14** of different sizes, the large filaments **48** of the permeable shell **40** may have a transverse dimension or diameter that is about 0.001 inches to about 0.004 inches and the small filaments **50** may have a transverse dimension or diameter of about 0.0004 inches to about 0.0015 inches, more specifically, about 0.0004 inches to about 0.001 inches. In addition, a difference in transverse dimension or diameter between the small filaments **50** and the large filaments **48** may be less than about 0.004 inches, more specifically, less than about 0.0035 inches, and even more specifically, less than about 0.002 inches. For embodiments of permeable shells **40** that include filaments **14** of different sizes, the number of small filaments **50** of the permeable shell **40** relative to the number of large filaments **48** of the permeable shell **40** may

be about 2 to 1 to about 15 to 1, more specifically, about 2 to 1 to about 12 to 1, and even more specifically, about 4 to 1 to about 8 to 1.

(49) The expanded relaxed state of the permeable shell **40**, as shown in FIG. **4**, has an axially shortened configuration relative to the constrained state such that the proximal hub **68** is disposed closer to the distal hub **66** than in the constrained state. Both hubs **66** and **68** are disposed substantially concentric to the longitudinal axis **46** of the device and each filamentary element **14** forms a smooth arc between the proximal and distal hubs **66** and **68** with a reverse bend at each end. A longitudinal spacing between the proximal and distal hubs **66** and **68** of the permeable shell **40** in a deployed relaxed state may be about 25 percent to about 75 percent of the longitudinal spacing between the proximal and distal hubs **66** and **68** in the constrained cylindrical state, for some embodiments. The arc of the filaments **14** between the proximal and distal ends **32** and **34** may be configured such that a middle portion of each filament **14** has a second transverse dimension substantially greater than the first transverse dimension.

(50) For some embodiments, the permeable shell **40** may have a first transverse dimension in a collapsed radially constrained state of about 0.2 mm to about 2 mm and a second transverse dimension in a relaxed expanded state of about 4 mm to about 30 mm. For some embodiments, the second transverse dimension of the permeable shell **40** in an expanded state may be about 2 times to about 150 times the first transverse dimension, more specifically, about 10 times to about 25 times the first or constrained transverse dimension. A longitudinal spacing between the proximal end **32** and distal end **34** of the permeable shell **40** in the relaxed expanded state may be about 25% percent to about 75% percent of the spacing between the proximal end **32** and distal end **34** in the constrained cylindrical state. For some embodiments, a major transverse dimension of the permeable shell **40** in a relaxed expanded state may be about 4 mm to about 30 mm, more specifically, about 9 mm to about 15 mm, and even more specifically, about 4 mm to about 8 mm.

(51) An arced portion of the filaments **14** of the permeable shell **40** may have a sinusoidal-like shape with a first or outer radius **88** and a second or inner radius **90** near the ends of the permeable shell **40** as shown in FIG. **6**. This sinusoid-like or multiple curve shape may provide a concavity in the proximal end **32** that may reduce an obstruction of flow in a parent vessel adjacent a vascular defect. For some embodiments, the first radius **88** and second radius **90** of the permeable shell **40** may be between about 0.12 mm to about 3 mm. For some embodiments, the distance between the proximal end **32** and distal end **34** may be less than about 60% of the overall length of the permeable shell **40** for some embodiments. Such a configuration may allow for the distal end **34** to flex downward toward the proximal end **32** when the device **10** meets resistance at the distal end **34** and thus may provide longitudinal conformance. The filaments **14** may be shaped in some embodiments such that there are no portions that are without curvature over a distance of more than about 2 mm. Thus, for some embodiments, each filament **14** may have a substantially continuous curvature. This substantially continuous curvature may provide smooth deployment and may reduce the risk of vessel perforation. For some embodiments, one of the ends **32** or **34** may be retracted or everted to a greater extent than the other so as to be more longitudinally or axially conformal than the other end.

(52) The first radius **88** and second radius **90** of the permeable shell **40** may be between about 0.12 mm to about 3 mm for some embodiments. For some embodiments, the distance between the proximal end **32** and distal end **34** may be more than about 60% of the overall length of the expanded permeable shell **40**. Thus, the largest longitudinal distance between the inner surfaces may be about 60% to about 90% of the longitudinal length of the outer surfaces or the overall length of device **10**. A gap between the hubs **66** and **68** at the proximal end **32** and distal end **34** may allow for the distal hub **66** to flex downward toward the proximal hub **68** when the device **10** meets resistance at the distal end and thus provides longitudinal conformance. The filaments **14** may be shaped such that there are no portions that are without curvature over a distance of more than about 2 mm. Thus, for some embodiments, each filament **14** may have a substantially

continuous curvature. This substantially continuous curvature may provide smooth deployment and may reduce the risk of vessel perforation. The distal end **34** may be retracted or everted to a greater extent than the proximal end **32** such that the distal end portion of the permeable shell **40** may be more radially conformal than the proximal end portion. Conformability of a distal end portion may provide better device conformance to irregular shaped aneurysms or other vascular defects. A convex surface of the device may flex inward forming a concave surface to conform to curvature of a vascular site.

(53) FIG. **10** shows an enlarged view of the filaments **14** disposed within a proximal hub **68** of the device **10** with the filaments **14** of two different sizes constrained and tightly packed by an outer ring of the proximal hub **68**. The tether member **72** may optionally be disposed within a middle portion of the filaments **14** or within the cavity **70** of the proximal hub **68** proximal of the proximal ends **60** of the filaments **14** as shown in FIG. **6**. The distal end of the tether **72** may be secured with a knot **92** formed in the distal end thereof which is mechanically captured in the cavity **70** of the proximal hub **68** formed by a proximal shoulder portion **94** of the proximal hub **68**. The knotted distal end **92** of the tether **72** may also be secured by bonding or potting of the distal end of the tether **72** within the cavity **70** and optionally amongst the proximal ends **60** of the filaments **14** with mechanical compression, adhesive bonding, welding, soldering, brazing or the like. The tether embodiment **72** shown in FIG. **6** has a knotted distal end **92** potted in the cavity of the proximal hub **68** with an adhesive. Such a tether **72** may be a dissolvable, severable or releasable tether that may be part of a delivery apparatus **111** used to deploy the device **10** as shown in FIG. **11** and FIGS. **23-26**. FIG. **10** also shows the large filaments **48** and small filaments **50** disposed within and constrained by the proximal hub **68** which may be configured to secure the large and small filaments **48** and **50** in place relative to each other within the outer ring of the proximal hub **68**.

(54) FIGS. **7** and **8** illustrate some configuration embodiments of braided filaments **14** of a permeable shell **40** of the device **10** for treatment of a patient's vasculature. The braid structure in each embodiment is shown with a circular shape **100** disposed within a pore **64** of a woven or braided structure with the circular shape **100** making contact with each adjacent filament segment. The pore opening size may be determined at least in part by the size of the filament elements **14** of the braid, the angle overlapping filaments make relative to each other and the picks per inch of the braid structure. For some embodiments, the cells or openings **64** may have an elongated substantially diamond shape as shown in FIG. **7**, and the pores or openings **64** of the permeable shell **40** may have a substantially more square shape toward a middle portion **30** of the device **10**, as shown in FIG. **8**. The diamond shaped pores or openings **64** may have a length substantially greater than the width particularly near the hubs **66** and **68**. In some embodiments, the ratio of diamond shaped pore or opening length to width may exceed a ratio of 3 to 1 for some cells. The diamond-shaped openings **64** may have lengths greater than the width thus having an aspect ratio, defined as Length/Width of greater than 1. The openings **64** near the hubs **66** and **68** may have substantially larger aspect ratios than those farther from the hubs as shown in FIG. **7**. The aspect ratio of openings **64** adjacent the hubs may be greater than about 4 to 1. The aspect ratio of openings **64** near the largest diameter may be between about 0.75 to 1 and about 2 to 1 for some embodiments. For some embodiments, the aspect ratio of the openings **64** in the permeable shell **40** may be about 0.5 to 1 to about 2 to 1.

(55) The pore size defined by the largest circular shapes **100** that may be disposed within openings **64** of the braided structure of the permeable shell **40** without displacing or distorting the filaments **14** surrounding the opening **64** may range in size from about 0.005 inches to about 0.01 inches, more specifically, about 0.006 inches to about 0.009 inches, even more specifically, about 0.007 inches to about 0.008 inches for some embodiments. In addition, at least some of the openings **64** formed between adjacent filaments **14** of the permeable shell **40** of the device **10** may be configured to allow blood flow through the openings **64** only at a velocity below a thrombotic threshold velocity. For some embodiments, the largest openings **64** in the permeable shell structure

40 may be configured to allow blood flow through the openings **64** only at a velocity below a thrombotic threshold velocity. As discussed above, the pore size may be less than about 0.016 inches, more specifically, less than about 0.012 inches for some embodiments. For some embodiments, the openings **64** formed between adjacent filaments **14** may be about 0.005 inches to about 0.04 inches.

(56) FIG. **12** illustrates in transverse cross section an embodiment of a proximal hub **68** showing the configuration of filaments which may be tightly packed and radially constrained by an inside surface of the proximal hub **68**. In some embodiments, the braided or woven structure of the permeable shell **40** formed from such filaments **14** may be constructed using a large number of small filaments. The number of filaments **14** may be greater than 125 and may also be between about 80 filaments and about 180 filaments. As discussed above, the total number of filaments **14** for some embodiments may be about 70 filaments to about 300 filaments, more specifically, about 100 filaments to about 200 filaments. In some embodiments, the braided structure of the permeable shell **40** may be constructed with two or more sizes of filaments **14**. For example, the structure may have several larger filaments that provide structural support and several smaller filaments that provide the desired pore size and density and thus flow resistance to achieve a thrombotic threshold velocity in some cases. For some embodiments, small filaments **50** of the permeable shell **40** may have a transverse dimension or diameter of about 0.0006 inches to about 0.002 inches for some embodiments and about 0.0004 inches to about 0.001 inches in other embodiments. The large filaments **48** may have a transverse dimension or diameter of about 0.0015 inches to about 0.004 inches in some embodiments and about 0.001 inches to about 0.004 inches in other embodiments. The filaments **14** may be braided in a plain weave that is one under, one over structure (shown in FIGS. **7** and **8**) or a supplementary weave; more than one warp interlace with one or more than one weft. The pick count may be varied between about 25 and 200 picks per inch (PPI).

(57) In alternative embodiments, occlusive devices that function as intrasaccular devices and utilize a softer exterior permeable shell and a stiffer interior structural shell to minimize the force applied by the distal end of the implant during deployment are described. Intrasaccular occlusive devices that include a permeable shell formed from a woven or braided mesh have been described in US 2017/0095254, US 2016/0249934, US 2016/0367260, US 2016/0249937, US 2018/0000489, and 2018/0206849, all of which are hereby expressly incorporated by reference in their entirety for all purposes. As described with respect to other embodiments of permeable shells, the filaments may be made from metals and metal alloys such as nitinol, platinum, tungsten, nickel, and combinations thereof. All or a portion of the filaments may also be composite filaments, such as drawn filled tubes (DFT), as described in US 2016/0249934, which was previously incorporated by reference in its entirety for all purposes. The DFT may include a highly radiopaque core inside a tubing. For instance, the DFT may include a platinum core inside of a nitinol tubing.

(58) FIG. **13** depicts an intrasaccular device that has first **40** and second **140** permeable shells. Each permeable shell has a proximal end, a distal end, a longitudinal axis, and comprises a plurality of elongate resilient filaments. The filaments have a woven structure and are secured relative to each other at the proximal ends and distal ends of each of the permeable shells **40**, **140**. The permeable shells **40**, **140** of the device **110** each have a radially constrained elongated state configured for delivery within a microcatheter, with the thin woven filaments extending longitudinally from the proximal end to the distal end of each permeable shell radially adjacent each other along a length of the filaments. The permeable shells **40**, **140** each have an expanded relaxed state with a globular and longitudinally shortened configuration relative to the radially constrained state. In the expanded state, the woven filaments form the self-expanding resilient permeable shell **40**, **140** in a smooth path radially expanded from a longitudinal axis of the permeable shell between the proximal end and distal end. The woven structure of the filaments forming the permeable shells includes a plurality of openings in each permeable shell **40**, **140** formed between the woven filaments. The braided mesh of each permeable shell **40**, **140** defines an interior cavity. The

permeable shell **140** resides in the interior cavity of permeable shell **40**.

(59) The expanded states of the permeable shells **40**, **140** can each have a diameter of about 4 mm, alternatively about 5 mm, alternatively about 6 mm, alternatively about 7 mm, alternatively about 8 mm, alternatively about 9 mm, alternatively about 10 mm, alternatively about 11 mm. The expanded state of the permeable shells **40**, **140** can each have a height or length of about 2.6 mm, about 3 mm, about 3.6 mm, about 4 mm, about 4.6 mm, about 5 mm, about 5.6 mm, about 6 mm, about 6.6 mm, about 7 mm, about 7.6 mm, about 8 mm, about 8.6 mm, about 9 mm, about 9.6 mm, or about 10 mm. The expanded state of the interior permeable shell **140** may have a smaller diameter than the exterior permeable shell **40**. The expanded state of the interior permeable shell **140** may have a smaller or shorter height than the first exterior permeable shell **40**. Alternatively, the expanded state of the interior permeable shell **140** may have substantially the same height as the exterior permeable shell **40**. The expanded state of the interior permeable shell **140** may define a smaller interior volume than the volume defined by the expanded state of the exterior permeable shell **40**.

(60) The exterior permeable shell **40** may serve as a soft outer layer and be made from wires having a smaller diameter than the wires that make up the interior permeable shell **140**. The exterior permeable shell **40** may be made from a plurality of wires or filaments braided into a mesh, e.g., a tubular mesh. The exterior permeable shell **40** may be made from about 96 to about 240 wires or filaments, alternatively about 96 to 180 wires or filaments, alternatively about 108 to about 180 wires or filaments, alternatively about 96 wires or filaments or more, alternatively about 108 wires or filaments or more, alternatively about 150 wires or filaments or more, alternatively about 180 wires or filaments or more. The diameter of the wires or filaments making up the exterior permeable shell **40** may be between about 0.0005" to about 0.00075", alternatively about 0.0004" to about 0.0008", alternatively about 0.0003" to about 0.0009".

(61) The interior permeable shell **140** may serve as a stiffer, structural layer. The interior permeable shell **140** may be made from a plurality of wires or filaments braided into a mesh, e.g., a tubular mesh. The interior permeable shell **140** may be made from about 12 to about 64 wires or filaments, alternatively about 18 to 56 wires or filaments, alternatively about 18 to about 48 wires or filaments, alternatively about 12 wires or filaments or more, alternatively about 18 wires or filaments or more, alternatively about 24 wires or filaments or more, alternatively about 32 wires or filaments or more, alternatively about 48 wires or filaments or more, alternatively from less than about 64 wires, alternatively from less than about 56 wires, alternatively from less than about 48 wires, alternatively from less than about 36 wires, alternatively from less than about 24 wires. The diameter of the wires or filaments making up the interior permeable shell **140** may be between about 0.00125" to about 0.002", alternatively about 0.001" to about 0.002", alternatively about 0.001" to about 0.003".

(62) Each of the filaments of the plurality of filaments making up the exterior **40** and interior **140** permeable shells have a proximal and distal end. The proximal ends of the filaments of the exterior **40** and interior **140** permeable shells may be gathered in a single proximal marker band **175**. The device **110** may be attached to a delivery pusher **63** that is disposed within a catheter **61** by attaching the proximal marker band **175** to the distal end of the pusher **63**. The distal ends of the plurality of filaments forming the exterior permeable shell **40** may be gathered in a first distal marker band **171**. The distal ends of the plurality of filaments forming the interior permeable shell **140** may be gathered in a second distal marker band **181**.

(63) The braid ("alpha") angle of the exterior permeable shell **40** may be different, e.g., higher than the braid angle of the interior permeable shell **140**. The braid ("alpha") angle of the exterior permeable shell **40** may be at least about 1.2 times, alternatively at least about 1.5 times, alternatively at least about 1.8 times, alternatively at least about 2.0 times, alternatively at least about 3.0 times, alternatively at least about 4.0 times greater than the braid angle of the interior permeable shell. Braid angle may be the angle between the wire and axis along which the wire is

braided. The braid angle of the exterior permeable shell may range from about 25 degrees to about 50 degrees, alternatively from about 20 degrees to about 60 degrees, alternatively from about 25 degrees to about 45 degrees. As seen in FIGS. **14-15**, the mismatch of the braid angles of the exterior **40** and interior **140** permeable shells ensures that a substantial length of the exterior permeable shell **40** deploys before the inner structural layer (interior permeable shell **140**) exits the microcatheter, even if the two layers are nearly identical in deployed height (i.e., the height of the relative expanded shapes). The mismatch in braid angle may also result in separation between the first distal marker band **171** and the second distal marker band **181**, thereby mitigating the risk of interference between the two marker bands during deployment and recapture of the device **110**.

(64) The exterior permeable shell **40** may be less stiff than the interior permeable shell **140**. The exterior permeable shell **40** may have a radial stiffness or a normalized radial stiffness of between about 0.001 N/mm and about 0.025 N/mm, alternatively between about 0.001 N/mm and about 0.010 N/mm. The interior permeable shell **140** may have a radial stiffness or a normalized radial stiffness of between about 0.005 N/mm and about 0.025 N/mm, alternatively between about 0.010 N/mm and about 0.020 N/mm. The exterior permeable shell **40** may be at least about 10 times, alternatively at least about 7 times, alternatively at least about 5 times, alternatively at least about 4 times, alternatively at least about 3 times, alternatively at least about 2 times less stiff than the interior permeable shell **140**.

(65) The interior permeable shell **140** may have an average pore size that is greater than the average pore size of the exterior permeable shell **40**. The average pore size of the interior permeable shell **140** may be at least about 1.5 times, alternatively at least about 1.75, alternatively at least about 2.0, alternatively at least about 2.5, alternatively at least about 3.0, alternatively at least about 4.0, alternatively at least about 5.0, alternatively at least about 7.5, alternatively at least about 10.0 times greater than the average pore size of the exterior permeable shell **40**. Pore size may be the diameter of a circle that fits between adjacent wires. Pore size may vary depending on wire diameter, braid angle, and number of wires. The average pore size of the interior permeable shell **140** may be between about 150 microns and 1 mm, alternatively between about 200 microns and about 800 microns, alternatively between about 200 microns and about 700 microns, alternatively between about 200 microns and about 600 microns, alternatively between about 300 microns and about 700 microns, alternatively between about 200 microns and about 800 microns, alternatively between about 200 microns and about 500 microns, alternatively between about 400 microns and about 800 microns. The average pore size of the exterior permeable shell **40** may be between about 100 and about 400 microns, alternatively between about 50 microns and about 400 microns, alternatively between about 100 microns and about 300 microns, alternatively between about 100 microns and about 250 microns, alternatively between about 50 microns and about 250 microns, alternatively between about 100 microns and about 200 microns.

(66) The interior permeable shell **140** may have an average mesh density that is smaller than the exterior permeable shell **40**. The average mesh density of the interior permeable shell **140** may be at least about 1.5 times, alternatively at least about 1.75, alternatively at least about 2.0, alternatively at least about 2.5, alternatively at least about 3.0, alternatively at least about 4.0, alternatively at least about 5.0, alternatively at least about 7.5, alternatively at least about 10.0 times smaller than the average mesh density of the exterior permeable shell **40**. The average mesh density of the interior permeable shell **140** may be about 5% to about 45% metal, alternatively about 5% to about 40% metal, alternatively about 10% to about 40% metal, alternatively about 10% to about 30% metal. The average mesh density of the exterior permeable shell **40** may be between about 55% to about 65% metal, alternatively about 50% to about 70% metal, alternatively about 55% to about 60% metal, alternatively about 50% to about 60% metal.

(67) For some embodiments, the permeable shell **40**, **140** or portions thereof may be porous and may be highly permeable to liquids. In contrast to most vascular prosthesis fabrics or grafts which typically have a water permeability below 2,000 ml/min/cm² when measured at a pressure of

120 mmHg, the permeable shell **40** of some embodiments discussed herein may have a water permeability greater than about 2,000 ml/min/cm.^{sup.2}, in some cases greater than about 2,500 ml/min/cm.^{sup.2}. For some embodiments, water permeability of the permeable shell **40**, **140** or portions thereof may be between about 2,000 and 10,000 ml/min/cm.^{sup.2}, more specifically, about 2,000 ml/min/cm.^{sup.2} to about 15,000 ml/min/cm.^{sup.2}, when measured at a pressure of 120 mmHg.

(68) Device embodiments and components thereof may include metals, polymers, biologic materials and composites thereof. Suitable metals include zirconium-based alloys, cobalt-chrome alloys, nickel-titanium alloys, platinum, tantalum, stainless steel, titanium, gold, and tungsten. Potentially suitable polymers include but are not limited to acrylics, silk, silicones, polyvinyl alcohol, polypropylene, polyvinyl alcohol, polyesters (e.g. polyethylene terephthalate or PET), PolyEtherEther Ketone (PEEK), polytetrafluoroethylene (PTFE), polycarbonate urethane (PCU) and polyurethane (PU). Device embodiments may include a material that degrades or is absorbed or eroded by the body. A bioresorbable (e.g., breaks down and is absorbed by a cell, tissue, or other mechanism within the body) or bioabsorbable (similar to bioresorbable) material may be used. Alternatively, a bioerodable (e.g., erodes or degrades over time by contact with surrounding tissue fluids, through cellular activity or other physiological degradation mechanisms), biodegradable (e.g., degrades over time by enzymatic or hydrolytic action, or other mechanism in the body), or dissolvable material may be employed. Each of these terms is interpreted to be interchangeable. bioabsorbable polymer. Potentially suitable bioabsorbable materials include polylactic acid (PLA), poly(alpha-hydroxy acid) such as poly-L-lactide (PLLA), poly-D-lactide (PDLA), polyglycolide (PGA), polydioxanone, polycaprolactone, polygluconate, polylactic acid-polyethylene oxide copolymers, modified cellulose, collagen, poly(hydroxybutyrate), polyanhydride, polyphosphoester, poly(amino acids), or related copolymer materials. An absorbable composite fiber may be made by combining a reinforcement fiber made from a copolymer of about 18% glycolic acid and about 82% lactic acid with a matrix material consisting of a blend of the above copolymer with about 20% polycaprolactone (PCL).

(69) Permeable shell embodiments **40**, **140** may be formed at least in part of wire, ribbon, or other filamentary elements **14**, **114**. These filamentary elements **14** may have circular, elliptical, ovoid, square, rectangular, or triangular cross-sections. Permeable shell embodiments **40** may also be formed using conventional machining, laser cutting, electrical discharge machining (EDM) or photochemical machining (PCM). If made of a metal, it may be formed from either metallic tubes or sheet material.

(70) Device embodiments **10**, **110** discussed herein may be delivered and deployed from a delivery and positioning system **112** that includes a microcatheter **61**, such as the type of microcatheter **61** that is known in the art of neurovascular navigation and therapy. Device embodiments for treatment of a patient's vasculature **10**, **110** may be elastically collapsed and restrained by a tube or other radial restraint, such as an inner lumen **120** of a microcatheter **61**, for delivery and deployment. The microcatheter **61** may generally be inserted through a small incision **152** accessing a peripheral blood vessel such as the femoral artery or brachial artery. The microcatheter **61** may be delivered or otherwise navigated to a desired treatment site **154** from a position outside the patient's body **156** over a guidewire **159** under fluoroscopy or by other suitable guiding methods. The guidewire **159** may be removed during such a procedure to allow insertion of the device **10**, **110** secured to a delivery apparatus **111** of the delivery system **112** through the inner lumen **120** of a microcatheter **61** in some cases. FIG. **17** illustrates a schematic view of a patient **158** undergoing treatment of a vascular defect **160** as shown in FIG. **18**. An access sheath **162** is shown disposed within either a radial artery **164** or femoral artery **166** of the patient **158** with a delivery system **112** that includes a microcatheter **61** and delivery apparatus **111** disposed within the access sheath **162**. The delivery system **112** is shown extending distally into the vasculature of the patient's brain adjacent a vascular defect **160** in the patient's brain.

(71) Access to a variety of blood vessels of a patient may be established, including arteries such as the femoral artery **166**, radial artery **164**, and the like in order to achieve percutaneous access to a vascular defect **160**. In general, the patient **158** may be prepared for surgery and the access artery is exposed via a small surgical incision **152** and access to the lumen is gained using the Seldinger technique where an introducing needle is used to place a wire over which a dilator or series of dilators dilates a vessel allowing an introducer sheath **162** to be inserted into the vessel. This would allow the device to be used percutaneously. With an introducer sheath **162** in place, a guiding catheter **168** is then used to provide a safe passageway from the entry site to a region near the target site **154** to be treated. For example, in treating a site in the human brain, a guiding catheter **168** would be chosen which would extend from the entry site **152** at the femoral artery up through the large arteries extending around the heart through the aortic arch, and downstream through one of the arteries extending from the upper side of the aorta such as the carotid artery **170**. Typically, a guidewire **159** and neurovascular microcatheter **61** are then placed through the guiding catheter **168** and advanced through the patient's vasculature, until a distal end **151** of the microcatheter **61** is disposed adjacent or within the target vascular defect **160**, such as an aneurysm. Exemplary guidewires **159** for neurovascular use include the Synchro2® made by Boston Scientific and the Glidewire Gold Neuro® made by MicroVention Terumo. Typical guidewire sizes may include 0.014 inches and 0.018 inches. Once the distal end **151** of the catheter **61** is positioned at the site, often by locating its distal end through the use of radiopaque marker material and fluoroscopy, the catheter is cleared. For example, if a guidewire **159** has been used to position the microcatheter **61**, it is withdrawn from the catheter **61** and then the implant delivery apparatus **111** is advanced through the microcatheter **61**.

(72) Delivery and deployment of device embodiments **10**, **110** discussed herein may be carried out by first compressing the device **10**, **110** to a radially constrained and longitudinally flexible state as shown in FIG. **11**. The device **10**, **110** may then be delivered to a desired treatment site **154** while disposed within the microcatheter **61**, and then ejected or otherwise deployed from a distal end **151** of the microcatheter **61**. In other method embodiments, the microcatheter **61** may first be navigated to a desired treatment site **154** over a guidewire **159** or by other suitable navigation techniques. The distal end of the microcatheter **61** may be positioned such that a distal port of the microcatheter **61** is directed towards or disposed within a vascular defect **160** to be treated and the guidewire **159** withdrawn. The device **10**, **110** secured to a suitable delivery apparatus **111** may then be radially constrained, inserted into a proximal portion of the inner lumen **120** of the microcatheter **61** and distally advanced to the vascular defect **160** through the inner lumen **120**.

(73) Once disposed within the vascular defect **160**, the device **10**, **110** may then allowed to assume an expanded relaxed or partially relaxed state with the permeable shell **40**, **140** of the device spanning or partially spanning a portion of the vascular defect **160** or the entire vascular defect **160**. The device **10**, **110** may also be activated by the application of an energy source to assume an expanded deployed configuration once ejected from the distal section of the microcatheter **61** for some embodiments. Once the device **10** is deployed at a desired treatment site **154**, the microcatheter **61** may then be withdrawn.

(74) Some embodiments of devices for the treatment of a patient's vasculature **10**, **110** discussed herein may be directed to the treatment of specific types of defects of a patient's vasculature. For example, referring to FIG. **18**, an aneurysm **160** commonly referred to as a terminal aneurysm is shown in section. Terminal aneurysms occur typically at bifurcations in a patient's vasculature where blood flow, indicated by the arrows **172**, from a supply vessel splits into two or more branch vessels directed away from each other. The main flow of blood from the supply vessel **174**, such as a basilar artery, sometimes impinges on the vessel where the vessel diverges and where the aneurysm sack forms. Terminal aneurysms may have a well defined neck structure where the profile of the aneurysm **160** narrows adjacent the nominal vessel profile, but other terminal aneurysm embodiments may have a less defined neck structure or no neck structure. FIG. **19**

illustrates a typical berry type aneurysm **160** in section where a portion of a wall of a nominal vessel section weakens and expands into a sack like structure ballooning away from the nominal vessel surface and profile. Some berry type aneurysms may have a well defined neck structure as shown in FIG. **19**, but others may have a less defined neck structure or none at all. FIG. **19** also shows some optional procedures wherein a stent **173** or other type of support has been deployed in the parent vessel **174** adjacent the aneurysm. Also, shown is embolic material **176** being deposited into the aneurysm **160** through a microcatheter **61**. Either or both of the stent **173** and embolic material **176** may be so deployed either before or after the deployment of a device for treatment of a patient's vasculature **10**.

(75) Prior to delivery and deployment of a device for treatment of a patient's vasculature **10**, **110**, it may be desirable for the treating physician to choose an appropriately sized device **10**, **110** to optimize the treatment results. Some embodiments of treatment may include estimating a volume of a vascular site or defect **160** to be treated and selecting a device **10**, **110** with a volume that is substantially the same volume or slightly over-sized relative to the volume of the vascular site or defect **160**. The volume of the vascular defect **160** to be occluded may be determined using three-dimensional angiography or other similar imaging techniques along with software which calculates the volume of a selected region. The amount of over-sizing may be between about 2% and 15% of the measured volume. In some embodiments, such as a very irregular shaped aneurysm, it may be desirable to under-size the volume of the device **10**, **110**. Small lobes or "daughter aneurysms" may be excluded from the volume, defining a truncated volume which may be only partially filled by the device without affecting the outcome. A device **10**, **110** deployed within such an irregularly shaped aneurysm **160** is shown in FIG. **28** discussed below. Such a method embodiment may also include implanting or deploying the device **10**, **110** so that the vascular defect **160** is substantially filled volumetrically by a combination of device and blood contained therein. The device **10**, **110** may be configured to be sufficiently conformal to adapt to irregular shaped vascular defects **160** so that at least about 75%, in some cases about 80%, of the vascular defect volume is occluded by a combination of device **10**, **110** and blood contained therein.

(76) In particular, for some treatment embodiments, it may be desirable to choose a device **10**, **110** that is properly oversized in a transverse dimension so as to achieve a desired conformance, radial force and fit after deployment of the device **10**. FIGS. **20-22** illustrate a schematic representation of how a device **10**, **110** may be chosen for a proper fit after deployment that is initially oversized in a transverse dimension by at least about 10% of the largest transverse dimension of the vascular defect **160** and sometimes up to about 100% of the largest transverse dimension. For some embodiments, the device **10**, **110** may be oversized a small amount (e.g. less than about 1.5 mm) in relation to measured dimensions for the width, height or neck diameter of the vascular defect **160**.

(77) In FIG. **20**, a vascular defect **160** in the form of a cerebral aneurysm is shown with horizontal arrows **180** and vertical arrows **182** indicating the approximate largest interior dimensions of the defect **160**. Arrow **180** extending horizontally indicates the largest transverse dimension of the defect **160**. In FIG. **21**, a dashed outline **184** of a device for treatment of the vascular defect is shown superimposed over the vascular defect **160** of FIG. **20** illustrating how a device **10**, **110** that has been chosen to be approximately 20% oversized in a transverse dimension would look in its unconstrained, relaxed state. FIG. **22** illustrates how the device **10**, **110**, which is indicated by the dashed line **184** of FIG. **21** might conform to the interior surface of the vascular defect **160** after deployment whereby the nominal transverse dimension of the device **10**, **110** in a relaxed unconstrained state has now been slightly constrained by the inward radial force **185** exerted by the vascular defect **160** on the device **10**, **110**. In response, as the filaments **14**, **114** of the device **10**, **110** and thus the permeable shell **40**, **140** made therefrom have a constant length, the device **10**, **110** has assumed a slightly elongated shape in the axial or longitudinal axis of the device **10** so as to elongate and better fill the interior volume of the defect **160** as indicated by the downward arrow **186** in FIG. **22**.

(78) Once a properly sized device **10, 110** has been selected, the delivery and deployment process may then proceed. It should also be noted also that the properties of the device embodiments **10, 110** and delivery system embodiments **112** discussed herein generally allow for retraction of a device **10** after initial deployment into a defect **160**, but before detachment of the device **10, 110**. Therefore, it may also be possible and desirable to withdraw or retrieve an initially deployed device **10** after the fit within the defect **160** has been evaluated in favor of a differently sized device **10, 110**. An example of a terminal aneurysm **160** is shown in FIG. **23** in section. The tip **151** of a catheter, such as a microcatheter **61** may be advanced into or adjacent the vascular site or defect **160** (e.g. aneurysm) as shown in FIG. **24**. For some embodiments, an embolic coil or other vaso-occlusive device or material **176** (as shown for example in FIG. **19**) may optionally be placed within the aneurysm **160** to provide a framework for receiving the device **10, 110**. In addition, a stent **173** may be placed within a parent vessel **174** of some aneurysms substantially crossing the aneurysm neck prior to or during delivery of devices for treatment of a patient's vasculature discussed herein (also as shown for example in FIG. **19**). An example of a suitable microcatheter **61** having an inner lumen diameter of about 0.020 inches to about 0.022 inches is the Rapid Transit® manufactured by Cordis Corporation. Examples of some suitable microcatheters **61** may include microcatheters having an inner lumen diameter of about 0.026 inch to about 0.028 inch, such as the Rebar® by Ev3 Company, the Renegade Hi-Flow® by Boston Scientific Corporation, and the Mass Transit® by Cordis Corporation. Suitable microcatheters having an inner lumen diameter of about 0.031 inch to about 0.033 inch may include the Marksmen® by Chestnut Medical Technologies, Inc. and the Vasco 28® by Balt Extrusion. A suitable microcatheter **61** having an inner lumen diameter of about 0.039 inch to about 0.041 inch includes the Vasco 35 by Balt Extrusion. These microcatheters **61** are listed as exemplary embodiments only, other suitable microcatheters may also be used with any of the embodiments discussed herein.

(79) Detachment of the device **10, 110** from the delivery apparatus **111** may be controlled by a control switch **188** disposed at a proximal end of the delivery system **112**, which may also be coupled to an energy source **142**, which severs the tether **72** that secures the proximal hub **68** of the device **10** to the delivery apparatus **111**. While disposed within the microcatheter **61** or other suitable delivery system **112**, as shown in FIG. **11**, the filaments **14, 114** of the permeable shell **40, 140** may take on an elongated, non-everted configuration substantially parallel to each other and a longitudinal axis of the catheter **61**. Once the device **10, 110** is pushed out of the distal port of the microcatheter **61**, or the radial constraint is otherwise removed, the distal ends **62** of the filaments **14, 114** may then axially contract towards each other so as to assume the globular everted configuration within the vascular defect **160** as shown in FIG. **25**.

(80) The device **10, 110** may be inserted through the microcatheter **61** such that the catheter lumen **120** restrains radial expansion of the device **10, 110** during delivery. Once the distal tip or deployment port of the delivery system **112** is positioned in a desirable location adjacent or within a vascular defect **160**, the device **10, 110** may be deployed out the distal end of the catheter **61** thus allowing the device to begin to radially expand as shown in FIG. **25**. As the device **10, 110** emerges from the distal end of the delivery system **112**, the device **10, 110** expands to an expanded state within the vascular defect **160**, but may be at least partially constrained by an interior surface of the vascular defect **160**.

(81) Upon full deployment, radial expansion of the device **10, 110** may serve to secure the device **10, 110** within the vascular defect **160** and also deploy the permeable shell **40** across at least a portion of an opening **190** (e.g. aneurysm neck) so as to at least partially isolate the vascular defect **160** from flow, pressure or both of the patient's vasculature adjacent the vascular defect **160** as shown in FIG. **26**. The conformability of the device **10, 110**, particularly in the neck region **190** may provide for improved sealing. For some embodiments, once deployed, the permeable shell **40, 140** may substantially slow the flow of fluids and impede flow into the vascular site and thus reduce pressure within the vascular defect **160**. For some embodiments, the device **10, 110** may be

implanted substantially within the vascular defect **160**, however, in some embodiments, a portion of the device **10**, **110** may extend into the defect opening or neck **190** or into branch vessels.

(82) For some embodiments, as discussed above, the device **10**, **110** may be manipulated by the user to position the device **10**, **110** within the vascular site or defect **160** during or after deployment but prior to detachment. For some embodiments, the device **10**, **110** may be rotated in order to achieve a desired position of the device **10** and, more specifically, a desired position of the permeable shell **40**, **140**, **240**, **340**, **440**, prior to or during deployment of the device **10**, **110**. For some embodiments, the device **10**, **110** may be rotated about a longitudinal axis of the delivery system **112** with or without the transmission or manifestation of torque being exhibited along a middle portion of a delivery catheter being used for the delivery. It may be desirable in some circumstances to determine whether acute occlusion of the vascular defect **160** has occurred prior to detachment of the device **10**, **110** from the delivery apparatus **111** of the delivery system **112**. These delivery and deployment methods may be used for deployment within berry aneurysms, terminal aneurysms, or any other suitable vascular defect embodiments **160**. Some method embodiments include deploying the device **10**, **110** at a confluence of three vessels of the patient's vasculature that form a bifurcation such that the permeable shell **40** of the device **10**, **110** substantially covers the neck of a terminal aneurysm. Once the physician is satisfied with the deployment, size and position of the device **10**, **110**, the device **10**, **110** may then be detached by actuation of the control switch **188** by the methods described above and shown in FIG. **26**. Thereafter, the device **10**, **110** is in an implanted state within the vascular defect **160** to effect treatment thereof.

(83) FIG. **27** illustrates another configuration of a deployed and implanted device in a patient's vascular defect **160**. While the implantation configuration shown in FIG. **26** indicates a configuration whereby the longitudinal axis **46** of the device **10**, **110** is substantially aligned with a longitudinal axis of the defect **160**, other suitable and clinically effective implantation embodiments may be used. For example, FIG. **27** shows an implantation embodiment whereby the longitudinal axis **46** of the implanted device **10**, **110** is canted at an angle of about 10 degrees to about 90 degrees relative to a longitudinal axis of the target vascular defect **160**. Such an alternative implantation configuration may also be useful in achieving a desired clinical outcome with acute occlusion of the vascular defect **160** in some cases and restoration of normal blood flow adjacent the treated vascular defect. FIG. **28** illustrates a device **10**, **110** implanted in an irregularly shaped vascular defect **160**. The aneurysm **160** shown has at least two distinct lobes **192** extending from the main aneurysm cavity. The two lobes **192** shown are unfilled by the deployed vascular device **10**, **110**, yet the lobes **192** are still isolated from the parent vessel of the patient's body due to the occlusion of the aneurysm neck portion **190**.

(84) Markers, such as radiopaque markers, on the device **10**, **110** or delivery system **112** may be used in conjunction with external imaging equipment (e.g. x-ray) to facilitate positioning of the device or delivery system during deployment. Once the device is properly positioned, the device **10** may be detached by the user. For some embodiments, the detachment of the device **10**, **110** from the delivery apparatus **111** of the delivery system **112** may be affected by the delivery of energy (e.g. heat, radiofrequency, ultrasound, vibrational, or laser) to a junction or release mechanism between the device **10** and the delivery apparatus **111**. Once the device **10**, **110** has been detached, the delivery system **112** may be withdrawn from the patient's vasculature or patient's body **158**. For some embodiments, a stent **173** may be placed within the parent vessel substantially crossing the aneurysm neck **190** after delivery of the device **10**, **110**, as shown in FIG. **19** for illustration.

(85) For some embodiments, a biologically active agent or a passive therapeutic agent may be released from a responsive material component of the device **10**, **110**. The agent release may be affected by one or more of the body's environmental parameters or energy may be delivered (from an internal or external source) to the device **10**, **110**. Hemostasis may occur within the vascular defect **160** as a result of the isolation of the vascular defect **160**, ultimately leading to clotting and

substantial occlusion of the vascular defect **160** by a combination of thrombotic material and the device **10, 110**. For some embodiments, thrombosis within the vascular defect **160** may be facilitated by agents released from the device **10** and/or drugs or other therapeutic agents delivered to the patient.

(86) For some embodiments, once the device **10, 110** has been deployed, the attachment of platelets to the permeable shell **40** may be inhibited and the formation of clot within an interior space of the vascular defect **160**, device, or both promoted or otherwise facilitated with a suitable choice of thrombogenic coatings, anti-thrombogenic coatings or any other suitable coatings (not shown) which may be disposed on any portion of the device **10, 110** for some embodiments, including an outer surface of the filaments **14** or the hubs **66** and **68**. Such a coating or coatings may be applied to any suitable portion of the permeable shell **40**. Energy forms may also be applied through the delivery apparatus **111** and/or a separate catheter to facilitate fixation and/or healing of the device **10, 110** adjacent the vascular defect **160** for some embodiments. One or more embolic devices or embolic material **176** may also optionally be delivered into the vascular defect **160** adjacent permeable shell portion that spans the neck or opening **190** of the vascular defect **160** after the device **10** has been deployed. For some embodiments, a stent or stent-like support device **173** may be implanted or deployed in a parent vessel adjacent the defect **160** such that it spans across the vascular defect **160** prior to or after deployment of the vascular defect treatment device **10, 110**.

(87) In any of the above embodiments, the device **10, 110** may have sufficient radial compliance so as to be readily retrievable or retractable into a typical microcatheter **61**. The proximal portion of the device **10, 110**, or the device as a whole for some embodiments, may be engineered or modified by the use of reduced diameter filaments, tapered filaments, or filaments oriented for radial flexure so that the device **10, 110** is retractable into a tube that has an internal diameter that is less than about 0.7 mm, using a retraction force less than about 2.7 Newtons (0.6 lbf) force. The force for retrieving the device **10, 110** into a microcatheter **61** may be between about 0.8 Newtons (0.18 lbf) and about 2.25 Newtons (0.5 lbf).

(88) Engagement of the permeable shell **40, 140** with tissue of an inner surface of a vascular defect **160**, when in an expanded relaxed state, may be achieved by the exertion of an outward radial force against tissue of the inside surface of the cavity of the patient's vascular defect **160**, as shown for example in FIG. **29**. A similar outward radial force may also be applied by a proximal end portion and permeable shell **40, 140** of the device **10, 110** so as to engage the permeable shell **40** with an inside surface or adjacent tissue of the vascular defect **160**. Such forces may be exerted in some embodiments wherein the nominal outer transverse dimension or diameter of the permeable shell **40** in the relaxed unconstrained state is larger than the nominal inner transverse dimension of the vascular defect **160** within which the device **10, 110** is being deployed, i.e., oversizing as discussed above. The elastic resiliency of the permeable shell **40** and filaments **14** thereof may be achieved by an appropriate selection of materials, such as superelastic alloys, including nickel titanium alloys, or any other suitable material for some embodiments. The conformability of a proximal portion of the permeable shell **40, 140** of the device **10, 110** may be such that it will readily ovalize to adapt to the shape and size of an aneurysm neck **190**, as shown in FIGS. **20-22**, thus providing a good seal and barrier to flow around the device. Thus, the device **10, 110** may achieve a good seal, substantially preventing flow around the device without the need for fixation members that protrude into the parent vessel.

(89) Various aspects of the present subject matter are set forth below, in review of, and/or in supplementation to, the embodiments described thus far, with the emphasis here being on the interrelation and interchangeability of the following embodiments. In other words, an emphasis is on the fact that each feature of the embodiments can be combined with each and every other feature unless explicitly stated otherwise or logically implausible. The embodiments described herein are restated and expanded upon in the following paragraphs without explicit reference to the figures.

(90) In many embodiments, device for treatment of a patient's cerebral aneurysm includes: a first

permeable shell having a proximal end, a distal end, a radially constrained elongated state configured for delivery within a catheter lumen, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a plurality of elongate filaments that are woven together to form a mesh, the expanded state defining an interior cavity; and a second permeable shell having a proximal end, a distal end, a radially constrained elongated state configured for delivery within a catheter lumen, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a plurality of elongate filaments that are woven together to form a mesh, wherein the second permeable shell sits within the interior cavity of the first permeable shell, and wherein the first and second permeable shells each have an average mesh density, and wherein the average mesh density of the second permeable shell is smaller than the average mesh density of the first permeable shell.

(91) In some embodiments, each of the plurality of filaments forming the first permeable shell has a proximal and distal end, wherein the proximal ends of the plurality of filaments of the first permeable shell are gathered in a proximal marker band. In some embodiments, each of the plurality of filaments forming the second permeable shell has a proximal and distal end, wherein the proximal ends of the plurality of filaments of the second permeable shell are gathered in the proximal marker band. In some embodiments, the distal ends of the plurality of filaments forming the first permeable shell are gathered in a first distal marker band. In some embodiments, the distal ends of the plurality of filaments forming the second permeable shell are gathered in a second distal marker band.

(92) In some embodiments, the mesh of the first permeable shell has a different braid angle than the mesh of the second permeable shell.

(93) In some embodiments, the mesh of the first permeable shell is softer than the mesh of the second permeable shell.

(94) In some embodiments, a height of the expanded state of the second permeable shell is less than a height of the expanded state of the first permeable shell.

(95) In some embodiments, a height of the expanded state of the second permeable shell is substantially the same as a height of the expanded state of the first permeable shell.

(96) In some embodiments, each of the wires of the plurality of wires of the first permeable shell has a diameter between about 0.0005" and about 0.00075".

(97) In some embodiments, each of the wires of the plurality of wires of the second permeable shell has a diameter between about 0.00125" and about 0.002".

(98) In some embodiments, the first permeable shell is made from about 108 filaments or more.

(99) In some embodiments, the second permeable shell is made from between about 18 and 48 filaments.

(100) In some embodiments, the plurality of filaments forming the second permeable shell have a larger diameter than the plurality of filaments forming the first permeable shell.

(101) In some embodiments, a smaller number of filaments form the second permeable shell than the first permeable shell.

(102) In some embodiments, the first and second permeable shells each have an average pore size, and wherein the average pore size of the second permeable shell is larger than the average pore size of the first permeable shell. In some embodiments, the average pore size of the second permeable shell is between about 150 microns and about 1 mm. In some embodiments, the average pore size of the first permeable shell is between about 100 and about 400 microns. In some embodiments, the average pore size of the second permeable shell is at least about 2 greater than the average pore size of the first permeable shell. In some embodiments, the average mesh density of the second permeable shell is at least about 2 smaller than the average mesh density of the first permeable shell.

(103) In some embodiments, the first permeable shell has a first braid angle and the second permeable shell has a second braid angle, and wherein the first and second braid angles are

different.

(104) In some embodiments, the first permeable shell has a first braid angle and the second permeable shell has a second braid angle, and wherein the first braid angle is higher than the second braid angle.

(105) In many embodiments, a method for treating a cerebral aneurysm having an interior cavity and a neck includes the steps of: advancing an implant in a microcatheter to a region of interest in a cerebral artery, wherein the implant comprises: a first permeable shell having a proximal end, a distal end, a radially constrained elongated state configured for delivery within a catheter lumen, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a plurality of elongate filaments that are woven together to form a mesh, the expanded state defining an interior cavity; and a second permeable shell having a proximal end, a distal end, a radially constrained elongated state configured for delivery within a catheter lumen, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a plurality of elongate filaments that are woven together to form a mesh, wherein the second permeable shell sits within the interior cavity of the first permeable shell, and wherein the first and second permeable shells each have an average mesh density, and wherein the average mesh density of the second permeable shell is smaller than the average mesh density of the first permeable shell; deploying the implant within the cerebral aneurysm, wherein each of the first and second permeable shells expands to its expanded state in the interior cavity of the aneurysm; and withdrawing the microcatheter from the region of interest after deploying the implant.

(106) In some embodiments, the first permeable shell begins to deploy to the expanded state of the first permeable shell before the second permeable shell begins to deploy to the expanded state of the second permeable shell.

(107) In some embodiments, each of the plurality of filaments forming the first permeable shell has a proximal and distal end, wherein the proximal ends of the plurality of filaments of the first permeable shell are gathered in a proximal marker band. In some embodiments, each of the plurality of filaments forming the second permeable shell has a proximal and distal end, wherein the proximal ends of the plurality of filaments of the second permeable shell are gathered in the proximal marker band. In some embodiments, the distal ends of the plurality of filaments forming the first permeable shell are gathered in a first distal marker band. In some embodiments, the distal ends of the plurality of filaments forming the second permeable shell are gathered in a second distal marker band.

(108) In some embodiments, the mesh of the first permeable shell has a different braid angle than the mesh of the second permeable shell.

(109) In some embodiments, the mesh of the first permeable shell is softer than the mesh of the second permeable shell.

(110) In some embodiments, a height of the expanded state of the second permeable shell is less than a height of the expanded state of the first permeable shell.

(111) In some embodiments, a height of the expanded state of the second permeable shell is substantially the same as a height of the expanded state of the first permeable shell.

(112) In some embodiments, each of the wires of the plurality of wires of the first permeable shell has a diameter between about 0.0005" and about 0.00075".

(113) In some embodiments, each of the wires of the plurality of wires of the second permeable shell has a diameter between about 0.00125" and about 0.002".

(114) In some embodiments, the first permeable shell is made from about 108 filaments or more.

(115) In some embodiments, the second permeable shell is made from between about 18 and 48 filaments.

(116) In some embodiments, the plurality of filaments forming the second permeable shell have a larger diameter than the plurality of filaments forming the first permeable shell.

(117) In some embodiments, a smaller number of filaments form the second permeable shell than

the first permeable shell.

(118) In some embodiments, the first and second permeable shells each have an average pore size, and wherein the average pore size of the second permeable shell is larger than the average pore size of the first permeable shell. In some embodiments, the average pore size of the second permeable shell is between about 150 microns and about 1 mm. In some embodiments, the average pore size of the first permeable shell is between about 100 and about 400 microns. In some embodiments, the average pore size of the second permeable shell is at least about 2 greater than the average pore size of the first permeable shell.

(119) In some embodiments, the average mesh density of the second permeable shell is at least about 2 smaller than the average mesh density of the first permeable shell.

(120) In some embodiments, the first permeable shell has a first braid angle and the second permeable shell has a second braid angle, and wherein the first braid angle is higher than the second braid angle.

(121) Although the foregoing invention has, for the purposes of clarity and understanding, been described in some detail by way of illustration and example, it will be obvious that certain changes and modifications may be practiced which will still fall within the scope of the appended claims. All applications, publications, and references mentioned in this application are expressly incorporated by reference in their entirety for all purposes.

Claims

1. A method for treating a cerebral aneurysm having an interior cavity and a neck, comprising the steps of: advancing an implant coupled to a pusher in a microcatheter to a region of interest in a cerebral artery, wherein the implant comprises: a first permeable shell having a proximal end, a distal end, a radially constrained elongated state configured for delivery within a lumen of the microcatheter, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a first plurality of elongate filaments that are woven together to form a mesh, the expanded state defining an interior cavity, wherein each of the filaments of the plurality of filaments of the first permeable shell has a diameter between about 0.0005" and about 0.00075", and wherein the first plurality of elongate filaments comprises 96 filaments or more; and a second permeable shell having a proximal end, a distal end, a radially constrained elongated state configured for delivery within the lumen of the microcatheter, an expanded state with a longitudinally shortened configuration relative to the radially constrained state, and a second plurality of elongate filaments that are woven together to form a mesh, wherein the second permeable shell sits within the interior cavity of the first permeable shell, wherein the mesh of the first permeable shell has a different braid angle than the mesh of the second permeable shell, and wherein each of the second plurality of elongate filaments has a larger diameter than each of the first plurality of elongate filaments; advancing the pusher to advance the implant out of a distal end of the microcatheter, wherein a substantial length of the first permeable shell exits the microcatheter before the second permeable shell; deploying the implant within the cerebral aneurysm, wherein each of the first and second permeable shells expands to its expanded state in the interior cavity of the aneurysm; and withdrawing the microcatheter from the region of interest after deploying the implant.

2. The method of claim 1, wherein the first permeable shell begins to deploy to the expanded state of the first permeable shell before the second permeable shell begins to deploy to the expanded state of the second permeable shell.

3. The method of claim 1, wherein a height of the expanded state of the second permeable shell is substantially the same as a height of the expanded state of the first permeable shell.

4. The method of claim 1, wherein each of the first plurality of filaments forming the first permeable shell has a proximal and distal end, wherein the proximal ends of the first plurality of

filaments of the first permeable shell are gathered in a proximal marker band.

5. The method of claim 4, wherein each of the second plurality of filaments forming the second permeable shell has a proximal and distal end, wherein the proximal ends of the second plurality of filaments of the second permeable shell are gathered in the proximal marker band.

6. The method of claim 4, wherein the distal ends of the first plurality of filaments forming the first permeable shell are gathered in a first distal marker band.

7. The method of claim 6, wherein the distal ends of the second plurality of filaments forming the second permeable shell are gathered in a second distal marker band.

8. The method of claim 1, wherein the first and second permeable shells each have an average mesh density, and wherein the average mesh density of the second permeable shell is smaller than the average mesh density of the first permeable shell.

9. The method of claim 1, wherein the mesh of the first permeable shell is softer than the mesh of the second permeable shell.

10. The method of claim 1, wherein each of the filaments of the second plurality of elongate filaments has a diameter between about 0.00125" and about 0.002".

11. The method of claim 1, wherein the first permeable shell is made from about 108 filaments or more.

12. The method of claim 1, wherein the second permeable shell is made from between about 18 and 48 filaments.

13. The method of claim 1, wherein a smaller number of filaments form the second permeable shell than the first permeable shell.

14. The method of claim 1, wherein the first and second permeable shells each have an average pore size, and wherein the average pore size of the second permeable shell is larger than the average pore size of the first permeable shell.

15. The method of claim 14, wherein the average pore size of the second permeable shell is between about 150 microns and about 1 mm.

16. The method of claim 14, wherein the average pore size of the first permeable shell is between about 100 microns and about 400 microns.

17. The method of claim 14, wherein the average pore size of the second permeable shell is at least about 2 greater than the average pore size of the first permeable shell.

18. The method of claim 1, wherein the average mesh density of the second permeable shell is at least about 2 smaller than the average mesh density of the first permeable shell.

19. The method of claim 1, wherein the first permeable shell has a first braid angle and the second permeable shell has a second braid angle, and wherein the first braid angle is higher than the second braid angle.
