

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412681
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Selvamanickam; Venkat et al.

Hybrid round superconductor wires using Nb—Ti filaments

Abstract

A round superconductor wire, method for fabricating same, and method for detecting quench in the same are disclosed. A round superconductor wire includes a superconductor wire former and at least one superconductor tape wound on the superconductor wire former. Each superconductor tape includes a substrate, a buffer film stack overlying the substrate, and a superconductor film overlying the buffer film stack.

Inventors:	Selvamanickam; Venkat (Houston, TX), Kar; Soumen (Houston, TX)
Applicant:	University of Houston System (Houston, TX); AMPeers LLC (Houston, TX)
Family ID:	77492131
Appl. No.:	17/801984
Filed (or PCT Filed):	December 23, 2020
PCT No.:	PCT/US2020/066760
PCT Pub. No.:	WO2021/173216
PCT Pub. Date:	September 02, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20230099529 A1	Mar. 30, 2023

Related U.S. Application Data

us-provisional-application US 62980762 20200224

Publication Classification

Int. Cl.: H01B12/06 (20060101); H01B12/08 (20060101); H01B13/00 (20060101)

U.S. Cl.:

CPC H01B12/06 (20130101); H01B12/08 (20130101); H01B13/0036 (20130101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3173079	12/1964	McFee	336/200	H01B 12/02
4277705	12/1980	Rios	310/215	H02K 9/20
4711825	12/1986	Oberly	428/614	H01B 1/023
5532664	12/1995	Buckles	336/DIG.1	H01F 6/06
6591120	12/2002	Tanaka	505/231	H10N 60/203
6750399	12/2003	Daeumling	N/A	N/A
7774035	12/2009	Lee	505/231	H10N 60/203
8032196	12/2010	Wakana	505/190	H10N 60/0941
8283816	12/2011	Ohashi	310/52	H02K 55/02
8385994	12/2012	Kodama	505/231	G01R 33/3815
8442605	12/2012	Willen	505/230	H01B 12/16
8644897	12/2013	Ichiki	505/220	H10N 60/80
8716188	12/2013	Xie	29/599	H10N 60/203
8745851	12/2013	Wang	505/925	H10N 60/80
8802598	12/2013	Usoskin	505/238	H10N 60/30
8809236	12/2013	Oswald	427/63	H10N 60/0801
8809685	12/2013	Bianchetti	29/599	H01R 4/68
8983563	12/2014	Semerad	505/238	H01B 12/02
9691532	12/2016	Tosaka	N/A	H01F 6/065
9741472	12/2016	Kumakura	N/A	H01F 6/06
10128025	12/2017	Kurihara	N/A	H10N 60/0801
10453590	12/2018	Selvamanickam	N/A	H01B 12/06
10607753	12/2019	Selvamanickam	N/A	H10N 60/0828
10818416	12/2019	Selvamanickam	N/A	H01B 1/02

10916361	12/2020	Hayashi	N/A	H10N 60/0324
11289640	12/2021	Solovyov	N/A	H10N 60/0801
11393970	12/2021	Majkic	N/A	H10N 60/0464
11653575	12/2022	Schlenga	505/231	H10N 60/0128
12050139	12/2023	Takayasu	N/A	G01K 13/006
2002/0134574	12/2001	Hughey et al.	N/A	N/A
2016/0217890	12/2015	Kurokawa et al.	N/A	N/A
2016/0260526	12/2015	Otto	N/A	H01B 13/0016
2018/0151792	12/2017	Selvamanickam	N/A	N/A
2018/0158577	12/2017	Xu	N/A	B22F 7/04
2021/0358660	12/2020	Majkic	N/A	H01B 12/06
2023/0008754	12/2022	Tanaka	N/A	H10N 60/81
2023/0099529	12/2022	Selvamanickam	174/125.1	H01B 13/0036
2023/0274858	12/2022	Kadiyala	505/230	H01B 12/06
2025/0079047	12/2024	Hartwig	N/A	H01B 13/0006

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
102010040272	12/2011	DE	H01F 41/048
0463568	12/1991	EP	N/A
2835838	12/2014	EP	H01L 39/02
1576416	12/1979	GB	H01B 12/10
H0574235	12/1992	JP	N/A
H05182534	12/1992	JP	N/A
H06150736	12/1993	JP	N/A
H06196028	12/1993	JP	N/A
H06267344	12/1993	JP	N/A
H0714442	12/1994	JP	N/A
H0785735	12/1994	JP	N/A
H08315649	12/1995	JP	N/A
2749136	12/1997	JP	N/A
2007273139	12/2006	JP	N/A
2008192352	12/2007	JP	N/A
2009231201	12/2008	JP	N/A
5274895	12/2012	JP	N/A
2014034688	12/2013	JP	N/A
2018163738	12/2017	JP	N/A
100821209	12/2007	KR	N/A
20150021875	12/2014	KR	N/A
WO-2005096322	12/2004	WO	H01F 6/06
WO-2006035065	12/2005	WO	H01F 41/048

WO-2008007141	12/2007	WO	H01B 12/06
WO-2008044500	12/2007	WO	B21C 3/04
WO-2008048331	12/2007	WO	C23C 16/408
WO-2017047959	12/2016	WO	H01B 12/02
2020087069	12/2019	WO	N/A

OTHER PUBLICATIONS

Original and Translation of CN113718313 (Year: 2021). cited by examiner

Original and Translation of JP2000195349 (Year: 2000). cited by examiner

Original and Translation of JP2006185861 (Year: 2006). cited by examiner

Extended European Search Report issued Feb. 16, 2024 in counterpart European Patent Application No. 20921408.9 (11 pages). cited by applicant

Kar, Soumen et al. "Symmetric tape round REBCO wire with J_e (4.2K, 15 T) beyond 450 A mm⁻² at 15 mm bend radius: a viable candidate for future compact accelerator magnet application."

Superconductor Science and Technology, vol. 31, No. 4, Apr. 1, 2018. cited by applicant

Kar, Soumen et al. "Next-generation highly flexible round REBCO STAR wires with over 580 A mm⁻² at 4.2 K, 20 T for future compact magnets." Supercond. Sci. Technol. vol. 32 (Aug. 20, 2019) 10LT01. 7 pages. <https://doi.org/10.1088/1361-6668-ab3904>. cited by applicant

Shen, T. et al. "Stable, predictable and training-free operation of superconducting Bi-2212

Rutherford cable racetrack coils at the wire current density of 1000A/mm²." Scientific Reports, vol. 9, Jul. 15, 2019, pp. 1-9. <https://www.nature.com/articles/S41598-019-46629-3.pdf>. cited by applicant

International Search report mailed May 5, 2020 in counterpart International Application No. PCT/US2019/058355. cited by applicant

International Search report mailed Mar. 15, 2021 in counterpart International Application No. PCT/US2020/066760. cited by applicant

Barth, Christian. "Overview: HTS4F Fusion Workshop." Universite de Geneve, Jan. 27, 2014, pp. 1-24. cited by applicant

Van der Laan, D.C. "YBa₂Cu₃O_{7-δ} coated conductor cabling for low ac-loss and high-field magnet applications." Supercond. Sci. Technol. 22(2009) 065013 pp. 1-5. cited by applicant

Selvamanickam, V. et al. "High Performance 2G Wires: From R&D to Pilot-Scale Manufacturing." IEEE Transactions on Applied Superconductivity, vol. 19, No. 3, Jun. 2009. pp. 3225-3230. cited by applicant

Takayasu, M. et al. "Present Status and Recent Developments of the Twisted Stacked-Tape Cable Conductor." IEEE Transactions on Applied Superconductivity. vol. 26, No. 2, Mar. 2016. 10 pages. cited by applicant

Luo, W. et al. "Fabrication and Electromagnetic Characterization of Ultrasmall Diameter REBCO Wires." IEEE Transactions on Applied Superconductivity. vol. 27, No. Jun. 4, 2017. 5 pages. cited by applicant

Mulder, T. et al. "Development of REBCO-CORC Wires With Current Densities of 400-600 A/mm² at 10 T and 4.2 K." IEEE Transactions on Applied Superconductivity. vol. 28, No. 3, Mar. 2018. 4 pages. cited by applicant

Fleiter, J. et al. "Electrical characterization of REBCO Reobel cables." 2013 Supercond. Sci. Technol. 26, 065014 doi:10.1088/0953-2048/26/6/065014. 5 pages. cited by applicant

Kar, S. et al. "Ultra-Small Diameter Round REBCO Wire With Robust Mechanical Properties." IEEE Transactions on Applied Superconductivity. vol. 27, No. Jun. 4, 2017. 4 pages. cited by applicant

Luo, W. et al. "Superior critical current of Symmetric Tape Round (STAR) REBCO wires in ultra-high background fields up to 31.2 T." 2018 Supercond. Sci. Technol. 31 12LT01, 8 pages. cited by applicant

Majkic, G. et al. "Engineering current density over 5 kA mm⁻² at 4.2 K, 14 T in thick film REBCO tapes." 2018 Supercond. Sci. Technol. 31 10LT01, 8 pages. DOI: 10.1088/1361-6668/aad844. cited by applicant

Van der Laan, D.C. et al. "Record current density of 344 A mm⁻² at 4.2 K and 17 T in CORC® accelerator magnet cables." 2016 Supercond. Sci. Technol. 29 055009. doi: 10.1088/0953-2048/29/5/055009. 9 pages. cited by applicant

Takayasu, M. et al. "Development of REBCO Twisted Stacked-Tape Cables for Magnet Application." May 21-23, 2014, 1st Workshop on Accelerator Magnets in HTS and DESY, Hamburg, Germany. 27 pages.
https://indico.cern.ch/event/308828/contributions/1680713/attachments/589814/811821/WAMHTS-1_Takayasu.pdf. cited by applicant

Primary Examiner: Dole; Timothy J.

Assistant Examiner: Azam; Muhammed

Attorney, Agent or Firm: Blank Rome LLP

Background/Summary

CROSS REFERENCE TO RELATED APPLICATION(S) (1) This application is a 371 application of PCT/US2020/066760, filed on Dec. 23, 2020, which claims priority to U.S. provisional patent application No. 62/980,762, filed on Feb. 24, 2020, both of which are hereby incorporated herein by reference in their entireties.

FIELD

(1) The embodiments disclosed herein are in the field of superconductors. More particularly, the embodiments disclosed herein relate to round superconductor wires and methods for fabricating same, which, inter alia, achieve a round superconductor wire having improved engineering current density ($J_{sub.e}$) in high magnetic field applications when made in small diameters, and which may serve as a mechanism for quench detection.

BACKGROUND

(2) A promising high temperature superconductor (HTS) candidate for use in accelerator magnets is RE-Ba—Cu—O (REBCO, RE=rare earth) tape that is fabricated by a reel-to-reel thin film process. Two challenges with REBCO tape as compared to Nb—Ti, Nb₃Sn, and Bi-2212 wires are associated with their overall flat rather than round cross-sectional geometry and a wide (~12 mm) profile rather than a multifilamentary architecture. To address these issues, globally, there have been efforts on high-current multi-strand REBCO cable configurations for accelerator applications such as ROEBEL cables in a rectangular structure, twisted stacked tape cables, and conductor-on-round-core (CORC®) cables/wires. On the other hand, current round RE-Ba—Cu—O (REBCO, RE=rare earth) superconductor wires are limited in engineering current density ($J_{sub.e}$) levels of about 400 A/mm² at 20 T when made in diameters less than 2 mm. Problems in degradation of high-performance REBCO tapes when wound to such small diameters are limiting the $J_{sub.e}$ levels of the round wires.

(3) Therefore, there is a need to achieve increases in the $J_{sub.e}$ of round REBCO wires to substantially higher levels of about 1000 A/mm² at 20 T when wound to diameters less than 2 mm.

(4) Further, superconductor Symmetric Tape Round (STAR) wires made of REBCO tapes are limited in their $J_{sub.e}$ by the copper wire former which occupies about 20-30% of the STAR wire

cross-section. Since there is a lower limit for the diameter of the former on which the REBCO tapes can be wound to avoid deterioration of performance, small diameter STAR wires can consist of only a few REBCO tapes which limits their J.sub.e.

(5) Another issue with HTS wires and tapes is their slow quench propagation velocity which makes quench detection very difficult. It is essential to detect a quench early so as to avoid catastrophic failure of a HTS magnet. Detection of quench throughout the length of the wire used in a magnet would be very desirable.

(6) Thus, it is desirable to provide a hybrid round superconductor wire, method for fabricating same, and method for detecting quench in same that are able to overcome the above disadvantages.

(7) These and other advantages of the present invention will become more fully apparent from the detailed description of the invention herein below.

SUMMARY

(8) Embodiments are directed to a round superconductor wire including a superconductor wire former and at least one superconductor tape wound on the superconductor wire former. Each superconductor tape includes: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack.

(9) Embodiments are also directed to a method for fabricating a round superconductor wire. The method includes: providing a superconductor wire former; and winding a superconductor tape around the superconductor wire former. The superconductor tape includes: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack.

(10) Embodiments are further directed to a method for detecting quench in a round superconductor wire. The method includes: employing the round superconductor wire in a coil configuration, wherein the round superconductor wire comprises a superconductor tape and a superconductor wire former on which the superconductor tape is wound; and monitoring current or voltage distribution between the superconductor tape and the superconductor wire former.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The foregoing summary, as well as the following detailed description, will be better understood when read in conjunction with the appended drawings. For the purpose of illustration only, there is shown in the drawings certain embodiments. It's understood, however, that the inventive concepts disclosed herein are not limited to the precise arrangements and instrumentalities shown in the figures.

(2) FIG. 1A is a schematic and cross-sectional diagram illustrating a thin symmetric REBCO tape (or REBCO-containing tape), wherein a REBCO film is positioned near the geometric center, close to the neutral plane. The overall tape thickness even with a 20+ μ m thick copper stabilizer is small because of the use of a thin (22 μ m) Hastelloy substrate. The thin symmetric REBCO tape is one of a plurality of thin symmetric REBCO tapes used to make a round superconductor wire.

(3) FIG. 1B is a schematic and cross-sectional diagram illustrating another one of a plurality of thin symmetric REBCO tapes used to make a round superconductor wire.

(4) FIG. 2A is a cross-sectional view illustrating a Symmetric Tape Round (STAR) wire comprising a 1 mm diameter copper former and six symmetric REBCO tapes.

(5) FIG. 2B is a plan view illustrating a 10 meter long, 1.9 mm diameter STAR wire.

(6) FIG. 3 is a plot illustrating J.sub.e of a 1.75 mm diameter STAR wire made with 8 symmetric REBCO tapes on a 0.81 mm diameter copper former, measured in high magnetic fields at 4.2 K when bent to a radius of 15 mm.

(7) FIG. 4 is a cross-sectional view illustrating a hybrid STAR wire comprising a 0.79 mm diameter Nb—Ti-containing former and six layers of symmetric REBCO tapes.

(8) FIG. 5 is a flowchart illustrating an embodiment of a method for fabricating a round superconductor wire, in accordance with an embodiment.

(9) FIG. 6 is a flowchart illustrating an embodiment of a method for detecting quench in a round superconductor wire, in accordance with an embodiment.

(10) FIG. 7 is a plot illustrating magnetic field dependence of engineering current density of four hybrid STAR wires at 4.2 K, measured at a bend radius of 15 mm.

DETAILED DESCRIPTION

(11) It is to be understood that the figures and descriptions of the present invention may have been simplified to illustrate elements that are relevant for a clear understanding of the present embodiments, while eliminating, for purposes of clarity, other elements found in a typical round superconductor wire or typical method for fabricating a round superconductor wire. Those of ordinary skill in the art will recognize that other elements may be desirable and/or required in order to implement the present embodiments. However, because such elements are well known in the art, and because they do not facilitate a better understanding of the present embodiments, a discussion of such elements is not provided herein. It is also to be understood that the drawings included herewith only provide diagrammatic representations of the presently preferred structures of the present invention and that structures falling within the scope of the present embodiments may include structures different than those shown in the drawings. Reference will now be made to the drawings wherein like structures are provided with like reference designations.

(12) Before explaining at least one embodiment in detail, it should be understood that the concepts set forth herein are not limited in their application to the construction details or component arrangements set forth in the following description or illustrated in the drawings. It should also be understood that the phraseology and terminology employed herein are merely for descriptive purposes and should not be considered limiting.

(13) It should further be understood that any one of the described features may be used separately or in combination with other features. Other embodiments of devices, systems, methods, features, and advantages described herein will be or become apparent to one with skill in the art upon examining the drawings and the detailed description herein. It's intended that all such additional devices, systems, methods, features, and advantages be protected by the accompanying claims.

(14) For purposes of this disclosure, the terms “film” and “layer” may be used interchangeably.

(15) For purposes of this disclosure, the phrase “round superconductor wire” may refer to a substantially round superconductor wire.

(16) For purposes of this disclosure, the phrase “superconductor wire former” refers to a superconductor-containing wire former comprising, for example, a composite of a superconductor material and a (non-superconductor) metallic material or matrix.

(17) For purposes of this disclosure, if the term “stabilizer” is mentioned generally (i.e., without the modifiers “bottom” or “top”), it may refer to either the bottom stabilizer or top stabilizer.

(18) This disclosure describes round REBCO wires with improved engineering current density in high magnetic fields at, for example, liquid helium temperatures. STAR REBCO wires of diameters of 1.3 mm-2 mm (or smaller) have been fabricated using REBCO tapes wherein the REBCO film is positioned near the geometric center or near the neutral plane of the tape. Such STAR wires exhibit excellent tolerance to bend strain. Thus far, STAR wires have been fabricated with a former made entirely of copper. This description uses a superconducting/superconductor former for STAR wires, hence “hybrid STAR wires”. Hybrid STAR wires lead to substantial improvement in $J_{sub.e}$ and also serve as a mechanism for quench detection.

(19) By replacement of the copper wire used as a former in STAR wires with a superconductor wire former, this disclosure seeks to improve the $J_{sub.e}$ of STAR wires as well as provide a new method for quench detection. Using a, for example, Nb—Ti-containing superconductor wire former of approximately 1.1 mm or less (with a preferred diameter of 0.4-1.1 mm), STAR wires of diameters 1 to 3 mm have been fabricated by spiral winding of symmetric REBCO tapes over the

superconductor wire former. Since Nb—Ti is superconducting below 10 T, its $J_{sub.e}$ can add to the $J_{sub.e}$ of the REBCO tapes resulting in a higher $J_{sub.e}$ for the entire STAR wire. If Nb.sub.3Sn wire is used as a superconductor wire former, its $J_{sub.e}$ could be additive to the STAR wire's $J_{sub.e}$ even in fields up to 20 T. If MgB.sub.2 or Bi—Sr—Ca—Cu—O (BSCCO) round wires are used as a former, their $J_{sub.e}$ could be additive to the STAR wire's $J_{sub.e}$ even in fields above 20 T.

(20) Since the electromagnetic characteristics of REBCO tape is different from that of other superconductor wires, in the event of quench in a REBCO tape in a STAR wire, the distribution of current between the REBCO tape (i.e., the closest tape immediately adjacent the superconductor wire former) and the superconductor former could change. Such an abrupt change could be detected by monitoring any deviations in the voltage or current characteristics of the coil made with a STAR wire. This detection of an impending quench is desirable to shut down and protect the expensive magnet.

(21) In aspects of the disclosure, engineering current density ($J_{sub.e}$) levels of 400-1500 A/mm.sup.2 at 4.2 K, 20 T may be achieved and which are up to about six-times higher than that achieved by Nb.sub.3Sn round superconductors at 4.2 K, 20 T.

(22) In more detail, the inventors developed an innovative approach to fabricate round superconductor (e.g., REBCO) wires with high engineering current density and high tolerance to bending strain. These round superconductor wires may only be 1.6 to 2 mm in overall diameter and are made by winding narrow REBCO (rectangular) tapes on an approximately 1 mm diameter (or less) copper wire former. Such small diameter round superconductor wires are possible by the use of symmetric tapes where the REBCO film is positioned near the neutral plane of each wound tape. In other words, in each wound tape, the overall thickness of the combination of the various layers on either side of the centrally located REBCO film is substantial the same. Hence, the tapes are considered symmetric in this respect. Such a symmetric tape architecture is achieved by a strategic selection of the thickness of the top copper stabilizer to minimize the distance between the REBCO film and the neutral plane of the tape, which minimizes bending strains when the round wire is bent into small diameters. The substrate (e.g., Hastelloy, Inconel, Stainless Steel, Nichrome, Ni—W) itself is made thin, about 10-25 μ m, so as to enable good tolerance to bending strain. The overall thickness of the REBCO tape is about 3060 μ m including the copper stabilizer (see overall REBCO tape in FIG. 1A). A plurality of these REBCO tapes (e.g., six to eight in number), each about 2.5 mm in width, are wound on a copper wire former to yield a Symmetric Tape Round (STAR) wire. The copper wire former is strong in its axial direction while flexible enough for bending the STAR wire to a small diameter. STAR wires of this disclosure may be fabricated in lengths of, for example, 10 meters as shown in FIG. 2B.

(23) FIG. 1A, by way of example only, is a schematic and cross-sectional diagram illustrating a thin symmetric REBCO tape, wherein a REBCO film is positioned near the geometric center, close to the neutral plane. The overall tape thickness even with a 20+ μ m thick top copper stabilizer is small because of the use of a thin (22 μ m) Hastelloy substrate. The thin symmetric REBCO tape is one of a plurality of thin symmetric REBCO tapes used to make a round superconductor wire.

(24) FIG. 1B is a schematic and cross-sectional diagram illustrating another one of a plurality of thin symmetric REBCO tapes used to make a round superconductor wire.

(25) FIG. 2A, by way of example only, is a cross-sectional view illustrating a Symmetric Tape Round (STAR) wire comprising a 1 mm diameter copper former and six symmetric REBCO tapes.

(26) FIG. 2B, by way of example only, is a plan view illustrating a 10 meter long, 1.9 mm diameter STAR wire.

(27) FIG. 3, by way of example only, is a plot illustrating $J_{sub.e}$ of a 1.75 mm diameter STAR wire made with 8 symmetric REBCO tapes on a 0.81 mm diameter copper former, measured in high magnetic fields at 4.2 K when bent to a radius of 15 mm.

(28) FIG. 3 shows the exemplary performance of a STAR wire in high magnetic fields at 4.2 K.

This STAR wire was made by winding 8 layers of symmetric tape on a 0.81 mm diameter copper former. The first two layers were 2 mm wide tapes and the remainder six layers were 2.5 mm wide tapes. The overall diameter of the STAR wire was 1.75 mm. In a straight form, this wire exhibited a critical current of 571 A at 77 K, self-field, corresponding to an engineering current density of 238 A/mm.². When bent to a radius of 15 mm, the critical current was 494 A at 77 K, self-field, corresponding to an engineering current density of 206 A/mm.². At this bend radius, this wire exhibited a $J_{sub.e}$ of 402 A/mm.² at 20 T. Based on the alpha value of 0.82 in equation Eq. 1: $J_{sub.e}(B)=J_{sub.e}(0)B^{sup.-\alpha}$ Eq. 1

(29) the $J_{sub.e}$ at 15 T is projected to be 515 A/mm.².

(30) If round REBCO wires can be produced with excellent bend strain tolerance that can meet the stringent bend radius requirement of 15 mm and a $J_{sub.e}$ at 4.2 K, 20 T of 600 A/mm.² now and 1000 A/mm.² or more in the near future, REBCO coils made of multiple wound round REBCO wires that enable future high-field accelerator magnets can be produced. A challenge in achieving such high $J_{sub.e}$ levels is the degradation in the critical current of the round REBCO wires when made to small diameters of about 1-3 mm. This disclosure describes multiple embodiments to achieve high $J_{sub.e}$ in round REBCO wires such as those with these small diameters.

(31) Conventional round REBCO wires are made with nearly identical REBCO tapes wound in a spiral fashion over a round former. Each round REBCO wire may comprise REBCO tapes of the same or, alternatively, different structural dimensions and/or composition in the different layers of the multiple superconductor tapes. The REBCO tapes of this disclosure are spirally wound over a round superconductor former. A (e.g., steady) change in the structure of the REBCO tapes from the inner REBCO tape to the outer REBCO tape of a round REBCO-containing wire may be employed. Some layers/structures within a REBCO tape may not change from corresponding layers/structures in the previous underlying REBCO tape (e.g., in any of the embodiments below). The following different structures of REBCO tapes are disclosed: a. Thickness of copper stabilizer on the REBCO film side. b. Thickness of silver layer(s). c. Thickness of substrate. d. Thickness of REBCO film. e. Width of REBCO tape.

Exemplary Embodiments

(32) By replacement of the copper wire used as a former in STAR wires with a superconducting wire former, this disclosure seeks to improve the $J_{sub.e}$ of STAR wires as well as provide a new method for quench detection. Using a Nb—Ti-containing superconductor wire former of 0.4-1.1 mm diameter, hybrid STAR wires of diameters 1 to 3 mm may be fabricated by spiral winding of symmetric REBCO tapes over the superconductor wire former. Since Nb—Ti is superconducting below 10 T, its $J_{sub.e}$ can add to the $J_{sub.e}$ of the REBCO tapes resulting in a higher $J_{sub.e}$ for the entire STAR wire. Similarly, if a Nb.sub.3Sn-containing superconductor wire former is used, its $J_{sub.e}$ could be additive to the STAR wire's $J_{sub.e}$ even in fields up to 20 T. Alternatively, if either a MgB2-containing or Bi—Sr—Ca—Cu—O (BSCCO)-containing superconductor wire former is used, either former's $J_{sub.e}$ could be additive to the STAR wire's $J_{sub.e}$ even in fields above 20 T.

(33) Since the electromagnetic characteristics of REBCO tape is different from that of other superconductor wires, in the event of quench in a REBCO tape in a STAR wire, the distribution of current or voltage between the REBCO tape and the superconductor wire former could change. Such an abrupt change could be detected by monitoring any deviations in the current or voltage characteristics of the coil made with a STAR wire. This detection of an impending quench is desirable to shut down and protect the expensive magnet.

(34) FIG. 4, by way of example only, is a cross-sectional view illustrating a hybrid STAR wire comprising a 0.79 mm diameter Nb—Ti-containing former and six layers of symmetric REBCO tapes. More specifically, FIG. 4 displays a cross-section of a STAR wire made using a 0.79 mm diameter Nb—Ti/Cu superconducting wire former. The Nb—Ti composition is in the form of filaments, with the Nb—Ti/Cu wire former being a composite of copper matrix with embedded Nb

—Ti filaments. The Nb—Ti/Cu ratio in the Nb—Ti/Cu wire former is 1:1.25. Also shown in FIG. 4 are six symmetric REBCO tapes wound on the Nb—Ti/Cu wire former to an overall STAR wire diameter of 1.54 mm.

(35) Table 1 shows details of four hybrid STAR wires made with varying numbers of symmetric REBCO tapes wound on a 0.79 mm diameter Nb—Ti/Cu superconductor wire. For example, hybrid-STAR wire #4 is made with two 1.8 mm, four 2.5 mm, and two 2.6 mm wide symmetric REBCO tapes and exhibited a critical current $I_{sub.c}$ greater than 600 A at 77 K, self-field when bent to a radius of 15 mm. This value corresponds to a $J_{sub.e}$ greater than 274 A/mm².

(36) TABLE-US-00001 TABLE 1 Details of four hybrid STAR wires fabricated with a 0.79 mm diameter Nb—Ti/Cu superconductor wire former. Critical current measurements were conducted at a bend radius of 15 mm. Final $I_{sub.c}$ $J_{sub.e}$ STAR wire (A) at (A/mm²) Tape width Total # diameter 77 K, at 77 K, H-STAR # in each layer of tapes (mm) self-field self-field 1 1.8 mm × 2, 3 1.20 185 164 2.5 mm × 1 2 1.8 mm × 2, 4 1.30 262 198 2.5 mm × 2 3 1.8 mm × 2, 6 1.54 466 250 2.5 mm × 4 4 1.8 mm × 2, 8 1.67 >600 >274 2.5 mm × 4, 2.6 mm × 2

(37) The engineering current densities of the four hybrid STAR wires at 4.2 K in magnetic fields up to 31.2 T are shown in FIG. 7, measured when bent to a radius of 15 mm. Four STAR wires were contemplated. STAR wire #3 was tested at two different times—one up to 15 T and another from 14 to 31 T. “L” refers to the number of layers of tapes wound on the superconductor wire former. In this case, “L” is equal to the number of tapes shown in Table 1. “α” is the variable in the exponent shown in the equation (Eq. 1) above.

(38) As shown in FIG. 7, hybrid STAR wire #4 has the most number of layers and exhibits the highest $J_{sub.e}$ value of 739 A/mm² at 4.2 K, 15 T. This value compares with a $J_{sub.e}$ of 515 A/mm² of the STAR wire (having a copper wire former) whose plot is shown in FIG. 3. This STAR wire has a similar former diameter and overall diameter and the same number of REBCO tapes as hybrid STAR wire #4. Based on the alpha value for hybrid STAR wire #4, it is projected that its $J_{sub.e}$ will reach 600 A/mm² at 4.2 K, 20 T which compares with the measured value of 402 A/mm² at 20 T of the STAR wire plot shown in FIG. 3.

(39) The Nb—Ti/Cu superconductor wire former will be superconducting at 4.2 K in magnetic fields below 10 T. Therefore, it could potentially sustain some current in magnetic fields less than 10 T which would raise the overall $J_{sub.e}$. The slight upward deviation in the slope of the $J_{sub.e}$ (B (magnetic field)) plot of hybrid STAR wire #1 in magnetic fields below 10 T could be indicative of such current sharing between the REBCO tapes and the Nb—Ti/Cu superconductor wire former. Such current sharing is not feasible with a copper wire former because of its low current-carrying capability.

(40) In addition to increasing the $J_{sub.e}$ of STAR wires, the superconductor wire former has a potential to detect a quench event. Quench occurs when there is a sudden transition from superconducting state to a resistive state. In such a drastic transition, the enormous current flowing through the superconductor has to be halted to avoid a catastrophic damage to the superconducting coil or magnet. Quench propagation velocity of REBCO is notoriously low which makes it hard to detect a quench in time by conventional methods. In the scenario of current sharing between the REBCO tapes and the superconductor wire former, when quench occurs in the REBCO tapes, a redistribution of the current sharing could be detected by measuring the voltage or current across the coil. This redistribution of current could then be used as a method to detect quench and protect the coil/magnet.

(41) While examples given in this invention are based on Nb—Ti as the superconducting composition within the superconductor wire former for the hybrid STAR wire, the invention is applicable to superconductor wire formers comprising other superconductor compositions of a predominantly round geometry such as Nb₃Sn, MgB₂, Bi—Sr—Ca—Cu—O, and combinations thereof. In these cases, the current sharing between the REBCO tapes and superconductor wire former could extend to magnetic fields of 20 T and above.

(42) Embodiments are directed to a round superconductor wire including a superconductor wire former and at least one superconductor tape wound on the superconductor wire former. Each superconductor tape includes: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack. In an embodiment, the superconductor wire former comprises a composition selected from the group consisting of Nb—Ti, Nb.sub.3Sn, MgB.sub.2, Bi—Sr—Ca—Cu—O, and combinations thereof. In another embodiment, the superconductor wire former comprises a plurality of superconductor filaments. In another embodiment, the superconductor wire former comprises a composite comprising a plurality of superconductor filaments embedded within a non-superconducting metal matrix. In another embodiment, the superconductor wire former comprises a composite comprising a plurality of Nb—Ti filaments embedded within a copper matrix. In yet another embodiment, the at least one superconductor tape comprises at least two superconductor tapes. In a further embodiment, the round superconductor wire comprises a diameter of 1-3 mm, and the superconductor wire former comprises a diameter of 0.4-1.1 mm.

(43) By way of example only, FIG. 5 is a flowchart illustrating an embodiment of a method **500** for fabricating a round superconductor wire. In an embodiment, the method **500** includes: providing a superconductor wire former (block **502**); and winding a superconductor tape around the superconductor wire former (block **504**). The superconductor tape includes: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack. In an embodiment of the method, the superconductor wire former comprises a composition selected from the group consisting of Nb—Ti, Nb.sub.3Sn, MgB.sub.2, Bi—Sr—Ca—Cu—O, and combinations thereof. In another embodiment of the method, the superconductor wire former comprises a plurality of superconductor filaments. In another embodiment of the method, the superconductor wire former comprises a composite comprising a plurality of superconductor filaments embedded within a non-superconducting metal matrix. In another embodiment of the method, the superconductor wire former comprises a composite comprising a plurality of Nb—Ti filaments embedded within a copper matrix. In yet another embodiment of the method, the superconductor tape is a first superconductor tape, the method further includes winding a second superconductor tape around the first superconductor tape. The second superconductor tape includes: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack. This winding of a second superconductor tape around the first superconductor tape covers the situation where the second superconductor tape may or may not be in direct contact with the first superconductor tape. For example, other superconductor tapes may be between the first and second superconductor tapes. In a further embodiment of the method, the round superconductor wire comprises a diameter of 1-3 mm, and the superconductor wire former comprises a diameter of 0.4-1.1 mm.

(44) By way of example only, FIG. 6 is a flowchart illustrating an embodiment of a method **600** for detecting quench in a round superconductor wire. In an embodiment, the method **600** includes: employing the round superconductor wire in a coil configuration, wherein the round superconductor wire includes a superconductor tape and a superconductor wire former on which the superconductor tape is wound (block **602**); and monitoring current or voltage distribution between the superconductor tape and the superconductor wire former (block **604**). In an embodiment of the method for detecting quench, the superconductor wire former comprises a composition selected from the group consisting of Nb—Ti, Nb.sub.3Sn, MgB.sub.2, Bi—Sr—Ca—Cu—O, and combinations thereof. In another embodiment of the method for detecting quench, the superconductor wire former comprises a plurality of superconductor filaments. In another embodiment of the method for detecting quench, the superconductor wire former comprises a composite comprising a plurality of superconductor filaments embedded within a non-superconducting metal matrix. In yet another embodiment of the method for detecting quench, the superconductor wire former comprises a composite comprising a plurality of Nb—Ti filaments

embedded within a copper matrix. In a further embodiment of the method for detecting quench, the round superconductor wire comprises a diameter of 1-3 mm, and the superconductor wire former comprises a diameter of 0.4-1.1 mm.

(45) Although embodiments are described above with reference to REBCO tapes comprising REBCO superconductor films, the REBCO superconductor films described in any of the above embodiments may alternatively be superconductor films comprising different superconductor material(s). Such alternative is considered to be within the spirit and scope of the present invention, and may therefore utilize the advantages of the configurations and embodiments described above.

(46) The method steps in any of the embodiments described herein are not restricted to being performed in any particular order. Also, structures mentioned in any of the method embodiments may utilize structures mentioned in any of the device embodiments. Such structures may be described in detail with respect to the device embodiments only but are applicable to any of the method embodiments.

(47) Features in any of the embodiments described above may be employed in combination with features in other embodiments described above, such combinations are considered to be within the spirit and scope of the present invention.

(48) The contemplated modifications and variations specifically mentioned above are considered to be within the spirit and scope of the present invention.

(49) It's understood that the above description is intended to be illustrative, and not restrictive. The material has been presented to enable any person skilled in the art to make and use the concepts described herein, and is provided in the context of particular embodiments, variations of which will be readily apparent to those skilled in the art (e.g., some of the disclosed embodiments may be used in combination with each other). Many other embodiments will be apparent to those of skill in the art upon reviewing the above description. The scope of the embodiments herein therefore should be determined with reference to the appended claims, along with the full scope of equivalents to which such claims are entitled. In the appended claims, the terms “including” and “in which” are used as the plain-English equivalents of the respective terms “comprising” and “wherein.”

Claims

1. A round superconductor wire comprising: a superconductor wire former; and at least one superconductor tape wound on the superconductor wire former, each superconductor tape comprising: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack, wherein the superconducting wire has an engineering current density ($J_{sub.e}$) of 400-1500 A/mm² at 4.2 K, 20 T.
2. The round superconductor wire of claim 1, wherein the superconductor wire former comprises a composition selected from a group consisting of Nb—Ti, Nb₃Sn, MgB₂, Bi—Sr—Ca—Cu—O, and combinations thereof.
3. The round superconductor wire of claim 1, wherein the superconductor wire former comprises a plurality of superconductor filaments.
4. The round superconductor wire of claim 1, wherein the superconductor wire former comprises a composite comprising a plurality of superconductor filaments embedded within a non-superconducting metal matrix.
5. The round superconductor wire of claim 1, wherein the superconductor wire former comprises a composite comprising a plurality of Nb—Ti filaments embedded within a copper matrix.
6. The round superconductor wire of claim 1, wherein the at least one superconductor tape comprises at least two superconductor tapes.
7. The round superconductor wire of claim 1, wherein the round superconductor wire comprises a diameter of 1-3 mm, and the superconductor wire former comprises a diameter of 0.4-1.1 mm.
8. A method for fabricating a round superconductor wire, the method comprising: providing a

- superconductor wire former; and winding a superconductor tape around the superconductor wire former; wherein the superconductor tape comprises: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack, wherein the superconducting wire has an engineering current density ($J_{sub.e}$) of 400-1500 A/mm² at 4.2 K, 20 T.
9. The method of claim 8, wherein the superconductor wire former comprises a composition selected from a group consisting of Nb—Ti, Nb₃Sn, MgB₂, Bi—Sr—Ca—Cu—O, and combinations thereof.
10. The method of claim 8, wherein the superconductor wire former comprises a plurality of superconductor filaments.
11. The method of claim 8, wherein the superconductor wire former comprises a composite comprising a plurality of superconductor filaments embedded within a non-superconducting metal matrix.
12. The method of claim 8, wherein the superconductor wire former comprises a composite comprising a plurality of Nb—Ti filaments embedded within a copper matrix.
13. The method of claim 8, wherein the superconductor tape is a first superconductor tape, the method further comprises: winding a second superconductor tape around the first superconductor tape; wherein the second superconductor tape comprises: a substrate; a buffer film stack overlying the substrate; and a superconductor film overlying the buffer film stack.
14. The method of claim 8, wherein the round superconductor wire comprises a diameter of 1-3 mm, and the superconductor wire former comprises a diameter of 0.4-1.1 mm.
15. A method for detecting quench in a round superconductor wire, the method comprising: employing the round superconductor wire in a coil configuration, wherein the round superconductor wire comprises a superconductor tape and a superconductor wire former on which the superconductor tape is wound; and monitoring current or voltage distribution between the superconductor tape and the superconductor wire former.
16. The method of claim 15, wherein the superconductor wire former comprises a composition selected from a group consisting of Nb—Ti, Nb₃Sn, MgB₂, Bi—Sr—Ca—Cu—O, and combinations thereof.
17. The method of claim 15, wherein the superconductor wire former comprises a plurality of superconductor filaments.
18. The method of claim 15, wherein the superconductor wire former comprises a composite comprising a plurality of superconductor filaments embedded within a nonsuperconducting metal matrix.
19. The method of claim 15, wherein the superconductor wire former comprises a composite comprising a plurality of Nb—Ti filaments embedded within a copper matrix.
20. The method of claim 15, wherein the round superconductor wire comprises a diameter of 1-3 mm, and the superconductor wire former comprises a diameter of 0.4-1.1 mm.
-