

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250283795

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Ramotowski; Thomas S. et al.

Single Lap Shear Test Sample Creation Method

Abstract

A mold is configured to make several identical single lap shear test samples according standards at one time. The mold can be made from aluminum and cast pieces of silicone rubber. The mold's shorter sides have slots designed to hold rigid substrates. The rigid substrates are inserted into the slots after the area to be bonded has been coated with adhesive. The opposing slots for each sample are offset so that the substrates overlap by the prescribed amount in the standard in the center of the mold. Spacer pieces are provided between the substrates. The slots and spacer pieces hold the substrates rigidly together to ensure a thin adhesive bondline between the two rigid substrates.

Inventors: Ramotowski; Thomas S. (Tiverton, RI), Poirier; Anthony S. (Westport, MA)

Applicant: The United States of America, as represented by the Secretary of the Navy
(Newport, RI)

Family ID: 95486426

Appl. No.: 19/092179

Filed: March 27, 2025

Related U.S. Application Data

parent US division 17815964 20220729 parent-grant-document US 12287313 child US 19092179

Publication Classification

Int. Cl.: G01N3/62 (20060101); B29C33/30 (20060101); B29L31/40 (20060101); G01N3/24 (20060101)

U.S. Cl.:

CPC G01N3/62 (20130101); B29C33/30 (20130101); G01N3/24 (20130101); B29L2031/40

Background/Summary

CROSS REFERENCE TO OTHER PATENT APPLICATIONS [0001] This application is a divisional application and claims the benefit of the filing date of U.S. patent application Ser. No. 17/815,964; filed on Jul. 29, 2022; and entitled “Single Lap Shear Test Sample Mold” by the inventors, Thomas S. Ramotowski and Anthony S. Poirier.

BACKGROUND OF THE INVENTION

1) Field of the Invention

[0003] The present invention is directed to a mold for making multiple single lap shear test samples at one time.

2) Description of the Related Art

[0004] Single lap shear test samples are commonly made and evaluated to measure the shear strength of adhesive bonds. The ASTM D-1002 standard specifies the procedure for lap shear tests for metal-to-metal bonded specimens. The test is applicable for determining adhesive strength, surface preparation parameters, and adhesive environmental durability.

[0005] FIG. 1 shows a single lap shear test sample, indicated generally as **102**, as specified in the ASTM D-1002 standard. The test sample **102** consists of two rigid substrates **104** attached to each other via an overlapping joint **106**. The test sample **102** is 25.4 mm (1") wide, with an overlap of 12.7 mm (0.5") in the bonded area **108**. The recommended metal thickness is 1.62 mm (0.064") and the overall length of the test sample **102** should be 177.8 mm (7"). Adhesive is applied to each of the rigid substrates **104** in the area of the overlapping joint **106** and the adhesive is allowed to cure. Once cured, the test sample **102** is placed in the grips of a universal testing machine and pulled until rupture occurs.

[0006] The ASTM D-1002 standard provides a model that tells the experimenter what the single lap shear test sample should look like (giving dimensions for the size of the two sample substrates and the extent the adhesive should be applied to both substrates). There remains a need for a mold that can be used to make multiple single lap shear test samples at one time.

OBJECT AND SUMMARY OF THE INVENTION

[0007] It is an object of the present invention to provide a mold for making multiple identical single lap shear test samples at one time.

[0008] It is another object of the invention to provide a mold for making samples, according to the ASTM D-1002 standard.

[0009] It is yet another object of the present invention to provide a mold that ensures that the two rigid substrates of the single lap shear test samples remain aligned with each other.

[0010] It is a further object of the present invention to provide a mold that ensures that the area of overlap between the two rigid substrates (where the adhesive bond is located) is consistent from sample to sample.

[0011] The invention described herein is a mold that is sized and configured to make several identical single lap shear test samples, according to the ASTM D-1002 standard, at one time. In some embodiments, the mold is made from aluminum and cast pieces of silicone rubber. The mold's shorter sides have slots providing a close sliding fit designed to hold rigid substrates of the single lap shear test samples, according to the ASTM D-1002 standard. The rigid substrates are inserted into the slots after the area to be bonded has been coated with a thin layer of adhesive. The opposing slots for each sample are offset so that the substrates overlap in the center of the mold by the prescribed amount in the ASTM D-1002 standard. The slots hold the substrates rigidly together to ensure the overlapped portions are in close physical contact to ensure a thin adhesive bondline

between the two rigid substrates.

[0012] According to an embodiment of the invention, there is provided a device for making multiple single lap shear test samples. The device includes a base plate extending along a horizontal plane and having a pair of two opposite long side edges. A pair of sidewalls is attached to the pair of two opposite long side edges. A first end block is located on a first end of the base plate. The first end block extends between the pair of sidewalls and is attached to the pair of sidewalls. The first end block has a first plurality of sample receiver slots along an inner surface of the first end block. A second end block is located on a second end of the base plate. The second end block extends between the pair of sidewalls and is attached to the pair of sidewalls. The second end block has a second plurality of sample receiver slots along an inner surface of the second end block. The second plurality of sample receiver slots is aligned offset from the first plurality of sample receiver slots. Spacer pieces are provided for insertion between the substrates and between the substrates and sidewalls.

[0013] According to another embodiment of the invention, a mold has a base plate with two opposing long sides and two opposing short sides. Sidewalls are attached to the two opposing long sides of the base plate. The sidewalls are perpendicular to the base plate. End blocks are adjacent to the two opposing short sides of the base plate and attached to the sidewalls. The end blocks have a plurality of sample receiver slots along an inner surface thereof.

[0014] According to a method of simultaneously bonding a plurality of single lap shear test samples, a base plate extending along a horizontal plane and having a pair of two opposite long side edges. A pair of sidewalls is attached to the pair of two opposite long side edges. A first end block is located on a first end of the base plate. The first end block extends between the pair of sidewalls and is attached to the pair of sidewalls. The first end block has a first plurality of sample receiver slots along an inner surface of the first end block. A second end block is located on a second end of the base plate. The second end block extends between the pair of sidewalls and is attached to the pair of sidewalls. The second end block has a second plurality of sample receiver slots along an inner surface of the second end block. The second plurality of sample receiver slots is aligned offset from the first plurality of sample receiver slots. Single lap shear test samples having a pair of rigid substrates with an overlapping adhesive joint are provided. The rigid substrates of the single lap shear test samples are inserted into the sample receiver slots of the first end block and second end block. Spacer pieces are inserted between adjacent rigid substrates and between the sidewalls and the rigid substrates to hold the single lap shear specimens together.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0015] Other objects, features and advantages of the present invention will become apparent upon reference to the following description of the preferred embodiments and to the drawings, wherein corresponding reference characters indicate corresponding parts throughout the several views of the drawings and wherein:

[0016] FIG. 1 is a perspective view of a single lap shear test sample, according to the prior art;

[0017] FIG. 2 is a top view of a mold for making single lap shear test samples;

[0018] FIG. 3 is a side view of a mold for making single lap shear test samples; and

[0019] FIG. 4 is a top view of a mold for making single lap shear test samples containing test samples.

DETAILED DESCRIPTION OF THE INVENTION

[0020] Referring to the drawings, FIG. 2 and FIG. 3 show a mold, indicated generally as **10**, according to the present invention. The mold **10** can be used for making multiple single lap shear test samples **102**. The mold **10** includes a base plate **12**. The base plate **12** extends along a

horizontal plane having a first end **14**, a second end **16**, and a pair of two opposite side edges **18**. A pair of sidewalls **20** is attached to the pair of two opposite side edges **18** by removable fasteners **22**, such as screws or bolts. Each sidewall **20** is attached perpendicularly to one side edge **18** of the base plate **12**. A first end block **24** is located on the first end **14** of the base plate **12** and a second end block **26** is located on the second end **16** of the base plate **12**. The first end block **24** extends between the pair of sidewalls **20** and is attached to the pair of sidewalls **20** by removable fasteners **28**, such as screws or bolts. A first plurality of sample receiver slots, as typically shown at **30**, is provided along an inner surface **32** of the first end block **24**. The second end block **26** extends between the pair of sidewalls **20** and is attached to the pair of sidewalls **20** by removable fasteners **34**, such as screws or bolts. A second plurality of sample receiver slots, as typically shown at **36**, is provided along an inner surface **38** of the second end block **26**. The number of sample receiver slots in the first plurality of sample receiver slots **30** is the same as the number of sample receiver slots in the second plurality of sample receiver slots **36**. The opposing sample receiver slots **30**, **36** are in offset alignment so that the rigid substrates **104** overlap in the center of the mold **10** by the amount prescribed in the ASTM D-1002 standard.

[0021] Sample receiver slots **30**, **36** are provided with a depth “d” to properly overlap rigid substrates **104** at the center of the mold **10**. Sample receiver slots **30**, **36** preferably have a width “W” that provides a close sliding fit with the received rigid substrates **104**. The close sliding fit is optimal for keeping the rigid substrates **104** aligned and in contact with one another. Any kind of force or interference fit could cause difficulties in inserting the rigid substrates **104** or removing the test samples **102**.

[0022] The mold **10** described herein is designed to make six identical single lap shear test samples **102**, according to the ASTM D-1002 standard, at one time; however, the number of test samples **102** can vary depending on the number of sample receiver slots **30**, **36** in each of the first end block **24** and the second end block **26**. In some embodiments, the mold **10** is made of aluminum. Other appropriate materials can be used.

[0023] Referring now to FIG. 4, test samples **102** are placed in the mold **10** by inserting the rigid substrates **104** into the sample receiver slots **30**, **36** in each of the first end block **24** and the second end block **26**, after the area of the overlapping joint **106** to be bonded has been coated with a thin layer of adhesive. The sample receiver slots **30**, **36** provide a close sliding fit with the rigid substrates **104** to hold the test samples **102** firmly in place for curing. As noted above, the opposing sample receiver slots **30**, **36** for each test sample **102** are in offset alignment. The offset is the thickness of the rigid substrates **104** so that the rigid substrates **104** maintain angular alignment and overlap in the center of the mold **10** by the amount prescribed in the ASTM D-1002 standard.

[0024] In an optimal embodiment, end blocks **24** and **26** are identical parts. The sample receiver slots **30** and **36** are offset in the block such that when end blocks **24** and **26** are rotated for assembly a staggered collation effect is achieved. Sidewalls **20** are also identical. This approach simplifies manufacturing. Fewer unique parts to make also means fewer parts to keep track of.

[0025] While mold **10** is being used for creating test samples **102**, spacer pieces **40** and **42** are provided to immobilize rigid substrates **104**. The spacer pieces **40** and **42** are removable and positionable between the sidewalls **20** of the mold **10** and between the test samples **102**. In some embodiments, the spacer pieces **40** and **42** may be made of an elastomeric material, such as molded silicone rubber. Preferably, spacer pieces **40** are molded to conform to the space between adjacent test samples **102**, and spacer pieces **42** are molded to conform to the space between test sample **102** and sidewall **20**. Thus, spacer pieces **40** will have opposing faces with two surfaces having different levels. Spacer pieces **42** will have one face with two surfaces having different levels, and one opposed face having a single level surface.

[0026] The spacer pieces **40** and **42** keep the area of the overlap joint **106** between the two rigid substrates **104** in close contact with each other to ensure a uniform bond. The sample receiver slots **30**, **36** hold the rigid substrates **104** together to ensure the overlapped portions are in close physical

contact and the spacer pieces **40** ensure pressure is constantly applied to the bonded area **108** to ensure a uniform bond is formed. Intimate contact between the rigid substrates **104** in the overlap joint **106** is further ensured by the compressive force exerted on the rigid substrates **104** when all of the spacer pieces **40** and **42** are inserted and the sidewalls **20** are attached to the base plate **12**. The softness and flexibility of the spacer pieces **40** and **42** allow them to be easily inserted or removed from the mold **10**, as needed.

[0027] As noted above, the mold **10** described herein is designed to make six test samples **102**, at one time. If a smaller number of test samples **102** is desired, dummy samples made of rigid substrate pairs can be inserted into the sample receiver slots **30**, **36** to allow the spacer pieces **40** and **42** to maintain the proper pressure on the bondlines of the real samples in the mold **10**. The dummy samples are used to maintain compression on the test samples **102** while they cure in the mold **10** if fewer than six samples are being made. The dummy samples can be made of aluminum or other appropriate material and can be used to enable casting of the spacer pieces **40** and **42**. In other words, mold **10** with dummy samples can be used as a mold for casting spacer pieces **40** and **42**.

[0028] The mold **10** described herein enables several essentially identical single lap shear test samples **102** to be made at the same time. The mold **10** ensures that the opposing rigid substrates **104** remain in intimate contact with each other in the overlapping joint **106** (where the adhesive bond will form). The rigid substrates **104** are held in place by the sample receiver slots **30**, **36** in the end blocks **24**, **26** of the mold **10**, while also being in contact with the base plate **12** of the mold **10**. When the rigid substrates **104** are inserted properly into the sample receiver slots **30**, **36** (i.e., all the way up against the end of the slots in the end blocks **24**, **26** of the mold **10**), the overlapping joint **106** is exactly one-half of a square inch (as specified in the ASTM D-1002 standard). This allows the results obtained from each test sample **102** to be directly compared to other samples.

[0029] The mold **10** allows for different test samples **102** to be made using different adhesives at the same time (i.e., all samples being made in the mold do not need to be made using the same adhesive). Different temperature cure profiles can easily be accommodated by the use of the dummy samples. Real samples can be removed and replaced with dummy samples to allow samples to experience different temperature cures, or to allow samples to spend different amounts of time curing at room temperature or in an oven.

[0030] The mold **10** can be disassembled to aid in removal of the individual test samples **102** without stressing or damaging the bonded area **108**. Generally, the adhesives used to make the test samples **102** will not stick to the spacer pieces **40** and **42** of the mold **10** if the spacers are made from silicone rubber or RTV. When small amounts of cured adhesive become attached to the surfaces of the base plate **12**, the sidewalls **20**, or the spacer pieces **40**, **42** of the mold **10**, the mold **10** can be disassembled for cleaning.

[0031] The base plate **12** should be sprayed with a suitable mold release material prior to use to prevent the adhesive being used to make the test samples **102** from adhering to the base plate **12** (e.g., MS-122-AD aerosol mold release from Miller Stephenson Chemical Company or the like can be used for that purpose). Spacer pieces **40**, **42** made of silicone rubber usually do not need to be sprayed with mold release, because very few adhesives bond to silicone rubber.

[0032] The dimensions of the mold **10** can be modified to allow the use of rigid substrates **104** of different lengths, widths, and thicknesses. The rigid substrates **104** do not necessarily need to be made of metal. For example, they could be made from rigid plastics like fiberglass or polyetheretherketone (PEEK). The size of the mold **10** could also be modified to allow more or fewer than six single lap shear samples to be made at one time.

[0033] An alternative embodiment could be made that omits base plate **12**. Sidewalls **20** can be directly attached to end blocks **24** and **26**. Alignment of the rigid substrates **104** and spacer pieces **40** and **42** can be performed by leveling against a flat surface. Operation of the mold will be similar; however, handling operations may be more difficult because test samples **102** and spacer

pieces **40** and **42** can slip out of alignment. Adherence of test samples **102** to base plate **12** would no longer occur.

[0034] The invention has been described with references to specific embodiments. While particular values, relationships, materials, and steps have been set forth for purposes of describing concepts of the present disclosure, it will be appreciated by persons skilled in the art that numerous variations and/or modifications may be made to the invention as shown in the disclosed embodiments without departing from the spirit or scope of the basic concepts and operating principles of the invention as broadly described. It should be recognized that, in the light of the above teachings, those skilled in the art could modify those specifics without departing from the invention taught herein. Having now fully set forth certain embodiments and modifications of the concept underlying the present disclosure, various other embodiments as well as potential variations and modifications of the embodiments shown and described herein will obviously occur to those skilled in the art upon becoming familiar with such underlying concept. It is intended to include all such modifications, alternatives, and other embodiments insofar as they come within the scope of the appended claims or equivalents thereof. It should be understood, therefore, that the invention might be practiced otherwise than as specifically set forth herein. Consequently, the present embodiments are to be considered in all respects as illustrative and not restrictive.

[0035] Finally, any numerical parameters set forth in the specification and attached claims are approximations (for example, by using the term “about” or “approximately”) that may vary depending upon the desired properties sought to be obtained by the present disclosure. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of significant digits and by applying ordinary rounding.

Claims

1. A method for making multiple single lap shear test samples from rigid substrates comprising: providing a mold having a base plate extending along a horizontal plane and having a pair of two opposite long side edges and a first and second end, a pair of sidewalls attached perpendicularly to the base plate at each long side edge, first and second end blocks joined to the base plate on the first and second ends thereof wherein each end block has a plurality of sample receiver slots formed therein and positioned to face complimentary sample receiver slots formed in the other end block; applying adhesive to an overlap region of at least one of the rigid substrates; inserting the rigid substrates into the end block sample receiver slots; inserting spacer pieces into the mold between adjacent rigid substrates and in between sidewalls and rigid substrates; allowing the adhesive applied to the overlap region between the rigid substrates to cure; and removing spacer pieces and cured rigid substrates from the mold, the cured rigid substrates being joined as single lap shear test samples.
2. The method of claim 1, further comprising the step of spraying the mold with a release agent before said step of inserting the rigid substrates into the end block sample receiver slots.
3. The method of claim 1, wherein the number of rigid substrates is fewer than the number of sample receiver slot pairs in the end blocks; and further comprising the steps of providing dummy rigid substrate pairs for each empty sample receiver slot pair having the same external dimensions as the rigid substrates; and inserting the dummy rigid substrate pair in each empty sample receiver slot pair before said step of inserting spacer pieces.
4. The method of claim 1, wherein the spacer pieces are provided before the step of inserting, the spacer pieces conforming to a space between adjacent inserted rigid substrates and a space between the inserted rigid substrate and the sidewall.
5. The method of claim 1 wherein the step of removing spacer pieces and cured rigid substrates from the mold comprises disassembling the mold.

6. A method for making multiple single lap shear test samples from rigid substrates comprising: providing a mold having a pair of sidewalls joined between a first end block and a second end block, each of said first and second end blocks having a plurality of sample receiver slots formed therein and positioned to face complimentary sample receiver slots formed in the other end block; applying adhesive to an overlap region of at least one of the rigid substrates; inserting the rigid substrates into the end block sample receiver slots; inserting spacer pieces into the mold between adjacent rigid substrates and in between sidewalls and rigid substrates; aligning the rigid substrates and the spacer pieces in the mold by leveling; allowing the adhesive applied to the overlap region between the rigid substrates to cure; and removing spacer pieces and cured rigid substrates from the mold, the cured rigid substrates being joined as single lap shear test samples.
