

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285643

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Xu; Weihao et al.

Hybrid Plasmonic Bottom Layer For Increased Near Field Transducer Reliability

Abstract

The present embodiments relate to a near field transducer for thermally-assisted magnetic recording (TAMR) with a hybrid plasmonic bottom layer. In a first example embodiment, a thermally-assisted magnetic recording (TAMR) write head is provided. The TAMR write head can include a main pole and a near field transducer (NFT). The NFT can include a first layer and a second layer. The first layer can include a first plasmonic material (e.g., rhodium, iridium, platinum). Further, the first layer can be disposed adjacent to the heat sink. The second layer can include a portion of a second plasmonic material (e.g., gold) and a first plasmonic portion (e.g., comprising rhodium). The first plasmonic portion of the second layer can be disposed adjacent to the ABS. The hybrid second layer (e.g., plasmonic bottom layer) can provide an improved NFT reliability during TAMR writing.

Inventors: Xu; Weihao (San Jose, CA), Maletzky; Tobias (San Jose, CA), Tanemura; Shigeki (Sunnyvale, CA), Fujii; Ken (San Jose, CA), Hu; Weisheng (Fremont, CA)

Applicant: Headway Technologies, Inc. (Milpitas, CA)

Family ID: 1000008618227

Appl. No.: 19/212279

Filed: May 19, 2025

Related U.S. Application Data

parent US continuation 18587570 20240226 parent-grant-document US 12354628 child US 19212279

Publication Classification

Int. Cl.: G11B5/31 (20060101); **G11B5/00** (20060101); **G11B5/187** (20060101); **G11B5/60** (20060101); **G11B13/08** (20060101)

U.S. Cl.:

CPC G11B5/314 (20130101); **G11B5/187** (20130101); **G11B5/6088** (20130101); **G11B13/08** (20130101); **G11B2005/0021** (20130101)

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS [0001] This application is a continuation of U.S. application Ser. No. 18/587,570, filed Feb. 26, 2024, the entire disclosure of which is hereby incorporated by reference.

TECHNICAL FIELD

[0002] Embodiments of the invention relate to the field of electro-mechanical data storage devices. More particularly, embodiments of the invention relate to the field of a near field transducer (NFT) structure of a thermally assisted magnetic recording (TAMR) device with a hybrid plasmonic bottom layer (PBL) portion.

BACKGROUND

[0003] A hard-disk drive (HDD) can include a non-volatile storage device that is housed in a protective enclosure and stores digitally encoded data on one or more circular disks having magnetic surfaces (a disk may also be referred to as a platter). When an HDD is in operation, each magnetic-recording disk can be rapidly rotated by a spindle system. Data can be written to a magnetic-recording disk using a write head which is positioned over a specific location of a disk. A write head can use a magnetic field to write data to the surface of a magnetic-recording disk.

[0004] In many cases, a write head can implement thermally assisted magnetic recording (TAMR) to interact with a magnetic recording medium (e.g., a disk). TAMR involves raising the temperature of a small region of the magnetic medium to near its Curie temperature where its coercivity and anisotropy are significantly reduced, and magnetic writing becomes easier to achieve even with weak write fields characteristic of small write heads in high recording density schemes. In TAMR, optical power from a light source can be converted into localized heating in a recording medium during a write process to temporarily reduce the field needed to switch the magnetizations of the medium grains. Thus, data storage density in a hard disk drive (HDD) in terms of thousands of tracks per inch (kTPI) can be further improved.

SUMMARY

[0005] The present embodiments relate to a near field transducer for a thermally-assisted magnetic recording (TAMR) with a hybrid plasmonic bottom layer. In a first example embodiment, a thermally-assisted magnetic recording (TAMR) write head is provided. The TAMR write head can include a main pole. The main pole can include a tip portion disposed adjacent to an air-bearing surface (ABS). The main pole can be configured to direct a magnetic field toward a magnetic recording medium to interact with the magnetic recording medium. The TAMR head can further include a heat sink disposed adjacent to the main pole.

[0006] The TAMR head can further include a near field transducer (NFT). The NFT can include a first layer and a second layer. The first layer can include a first plasmonic material (e.g., rhodium, iridium, platinum). Further, the first layer can be disposed adjacent to the heat sink.

[0007] The second layer can include a portion of a second plasmonic material (e.g., gold) and a first plasmonic portion (e.g., comprising rhodium). The portion of the first plasmonic material of the second layer can be disposed adjacent to the ABS.

[0008] In some instances, the NFT can include an alumina layer disposed between the waveguide and the second layer of the near field transducer. The alumina layer can include an etched recess recessed into the alumina layer. The etched recess can be etched into the alumina layer via an etching process (e.g., IBE).

[0009] In another example embodiment, a method for manufacturing a near field transducer that is part of a thermally-assisted magnetic recording (TAMR) write head is provided. The method can include disposing an alumina layer above a waveguide. The method can further include forming an etched recess in the alumina layer via an etching process. In some instances, the etching process comprises an ion beam etching (IBE) process.

[0010] The method can further include disposing a first plasmonic material in a first portion of the etched recess. In some instances, the method can further include disposing a photo-resist layer above the alumina layer. The photo-resist layer can define a length of the first layer. Further, the photo-resist layer can be removed, where the removing of the photo-resist layer removes part of the first plasmonic material remaining in the etched recess to expose the second portion of the etched recess.

[0011] The method can further include disposing a second plasmonic material in a second portion of the etched recess. The first plasmonic material and the second plasmonic material comprise a second layer of the near field transducer. Further, a portion of the full film of the second plasmonic material can be removed such that the second plasmonic material remains only in the second portion of the etched recess.

[0012] The method can further include disposing a first layer comprising the first plasmonic material above the alumina layer and the etched recess.

[0013] In some embodiments, a patterning mask can be disposed above the first layer. The patterning mask can define a final shape of the near field transducer. Further, a portion of the first layer not below the patterning mask can be removed.

[0014] Further, in some embodiments, the method can include disposing a cladding material adjacent to the first layer such that the first layer and the cladding material form a flat surface.

[0015] In another example embodiment, a near field transducer (NFT) is provided. The NFT can include a first layer comprising a first plasmonic material (e.g., rhodium, iridium, platinum). The first layer can be disposed adjacent to the heat sink. In some instances, the first layer is defined by a patterning mask added above the first layer. The patterning mask can define a final shape of the near field transducer.

[0016] The NFT can also include a second layer that can include a second plasmonic portion (e.g., comprising gold) and a first plasmonic portion (e.g., comprising rhodium, iridium, or platinum). The first plasmonic portion can be disposed adjacent to the ABS. The NFT can further include a waveguide.

[0017] In some instances, the write head can include an alumina layer disposed between the waveguide and the second layer of the near field transducer. The alumina layer can include an etched recess formed into the alumina layer via an etching process. The second layer can be disposed within the etched recess.

[0018] Other features and advantages of embodiments of the present invention will be apparent from the accompanying drawings and from the detailed description that follows.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0019] Embodiments of the present invention are illustrated by way of example and not limitation in the figures of the accompanying drawings, in which like references indicate similar elements and in which:

[0020] FIGS. 1A-B are cross-section views of an example self-aligned gold-rhodium (Au—Rh) bi-layer structure for a write head according to some embodiments.

[0021] FIG. 2 is a cross-section view of a write head with a hybrid PBL NFT according to some embodiments.

[0022] FIG. 3A illustrates a 3D, half-model representation of a PBL as part of a write head according to some embodiments.

[0023] FIG. 3B illustrates a 3D, half-model representation of a hybrid PBL as part of a write head according to some embodiments.

[0024] FIG. 4A is a cross-sectional view of a PBL according to some embodiments.

[0025] FIG. 4B is a cross-sectional view of a hybrid PBL according to some embodiments.

[0026] FIG. 5A illustrates the ADC for a write head with hybrid PBL as described herein compared to the ADC of a single material PBL write head for varying values of BSDh and PBLh2 according to some embodiments.

[0027] FIG. 5B is a graphical representation of a peg temperature at the recording point for varying values of BSDh and PBLh2 according to some embodiments.

[0028] FIG. 5C is a graphical representation of a laser current (I_{eff}) for varying values of BSDh and PBLh2 according to some embodiments.

[0029] FIG. 5D is a graphical representation of an Au temperature at the recording point for varying values of BSDh and PBLh2 according to some embodiments.

[0030] FIG. 6A is a cross-section view of a NFT with an alumina layer deposited on top of a waveguide according to some embodiments.

[0031] FIG. 6B is a top view of a NFT with an alumina layer deposited on top of a waveguide according to some embodiments.

[0032] FIG. 7A is a cross-section view of a NFT with an alumina layer after an IBE etching of the alumina layer according to some embodiments.

[0033] FIG. 7B is a top view of a NFT with an alumina layer after an IBE etching of the alumina layer according to some embodiments.

[0034] FIG. 8A is a cross-section view of a NFT with a full film deposition on top of the alumina layer according to some embodiments.

[0035] FIG. 8B is a top view of a NFT with a full film deposition on top of the alumina layer according to some embodiments.

[0036] FIG. 9A is a cross-section view of an NFT after a field RH removal and CMP/IBE according to some embodiments.

[0037] FIG. 9B is a top view of an NFT after a field RH removal and CMP/IBE according to some embodiments.

[0038] FIG. 10A is a cross-section view of an NFT with a photoresist being patterned to define a final Rh length according to some embodiments.

[0039] FIG. 10B is a top view of an NFT with a photoresist being patterned to define a final Rh length according to some embodiments.

[0040] FIG. 11A is a cross-section view of an NFT with the IBE process applied to pattern the Rh and the photoresist being stripped according to some embodiments.

[0041] FIG. 11B is a top view of an NFT with the IBE process applied to pattern the Rh and the photoresist being stripped according to some embodiments.

[0042] FIG. 12A is a cross-section view of an NFT with a full film Au layer being deposited on top of the alumina layer according to some embodiments.

[0043] FIG. 12B is a top view of an NFT with a full film Au layer being deposited on top of the alumina layer according to some embodiments.

[0044] FIG. 13A is a cross-section view of an NFT after the Au layer is removed according to some embodiments.

[0045] FIG. 13B is a top view of an NFT after the Au layer is removed according to some

embodiments.

[0046] FIG. **14A** is a cross-section view of an NFT with a full film Rh deposition according to some embodiments.

[0047] FIG. **14B** is a top view of an NFT with a full film Rh deposition according to some embodiments.

[0048] FIG. **15A** is a cross-section view of an NFT with a photolithography patterning process applied according to some embodiments.

[0049] FIG. **15B** is a top view of an NFT with a photolithography patterning process applied according to some embodiments.

[0050] FIG. **16A** is a cross-section view of an NFT after an etching process being applied to remove a portion of the Rh layer according to some embodiments.

[0051] FIG. **16B** is a top view of an NFT after an etching process being applied to remove a portion of the Rh layer according to some embodiments.

[0052] FIG. **17A** is a cross-section view of an NFT with a cladding material added according to some embodiments.

[0053] FIG. **17B** is a top view of an NFT with a cladding material added according to some embodiments.

DETAILED DESCRIPTION

[0054] A write head utilizing a thermally assisted magnetic recording (TAMR) technology can increase the amount of digital data capable of being stored on a magnetic recording medium (e.g., a disk) by temporarily heating the disk during writing. Heating the disk can make the disk more receptive to magnetic fields and allow for writing to smaller regions on the disk (thereby increasing the data storage capacity on the disk). Write heads utilizing TAMR are greatly increasing in popularity due to their ability to increase disk capacity. For example, TAMR can enable recording at 1~10 Tb/inch.^{sup.2} data density.

[0055] Utilizing the temperature dependence of a magnetic coercivity, write heads using TAMR can convert optical power into localized heating of the magnetic recording medium to temporarily reduce the switching field needed to align the magnetizations of the medium grains. Sharp thermal gradients can translate into high magnetic gradients that can enable a higher data storage density than with other magnetic recording technologies. Further, the heat spot size may need to be smaller than the diffraction limit of light, plasmonic structures, also referred to as near field transducers (NFTs), can be used to deliver the desirable confinement of the optical heating.

[0056] A primary challenge in TAMR recording can be to improve the reliability of the recording head due to the high operating temperature during TAMR recording. For example, the temperature during TAMR recording can be around the Curie temperature of an iron-platinum material (e.g., FePt with a Curie temperature ~420° C.).

[0057] FIGS. **1A-B** are cross-section views of an example self-aligned gold-rhodium (Au—Rh) bi-layer structure for a write head **100a-b**. As shown in FIGS. **1A-1B**, a magnetic pole **102** can be disposed adjacent to a heat sink **104**. A portion of the magnetic pole **102** can be disposed at an air-bearing surface **106**.

[0058] The write head **100** can further include a rhodium (Rh) layer **108** and a gold (Au) layer **110**. Rh layer **108** can be disposed adjacent to the heat sink **104**. Rh layer **108** and Au layer **110** can form a bi-layer structure as described herein. The write head **100** can also include an alumina (e.g., aluminum oxide) layer **112** and a waveguide core **114**. The write head as shown in FIG. **1A-B** can have good optical properties in the bottom layer (e.g., Au layer **110**) and robust materials in the top layer (e.g., Rh layer **108**) such as platinum (Pt), rhodium (Rh), and iridium (Ir). The bottom layer can serve as a plasmon generator transferring the light power from the waveguide mode into the plasmon mode. Further, the top layer, which can act as an antenna at the ABS transferring the power into the medium, can be more reliable under the high temperature ABS-environments during the TAMR writing process.

[0059] However, in many cases, densification of the bottom layer (e.g., Au layer **110**) may still occur during TAMR writing. This densification can lead to a recession of the bottom layer from the ABS, which can cause a reduction of NFT efficiency. This can reduce the temperature in the medium below a critical recording temperature, which can result in grains not being aligned with the writer's magnetic field.

[0060] The present embodiments relate to a Near Field Transducer (NFT) for use in a TAMR write head. Particularly, the NFT as described herein can include a dual metal plasmonic bottom layer (PBL) also referred to as hybrid PBL for the NFT. Additionally, the present embodiments provide methods for building the NFT as described herein.

[0061] The NFT can include a bottom layer (e.g., a plasmon generator). The bottom layer can include a material such as a hybrid Rh/Au (or Ir/Au, Pt/Au, etc.). The bottom layer can be disposed adjacent to a dielectric waveguide. The NFT can also include a top layer comprising a highly thermo-mechanically stable material such as Rh, disposed above the bottom layer and disposed closer to the heat sink. The NFT can further include a peg region with small cross-track and down-track dimension at the Air Bearing Surface (ABS).

[0062] FIG. 2 is a cross-section view of a write head **200** with a hybrid PBL NFT. As shown in FIG. 2, the write head **200** can include a bottom layer **202** disposed adjacent to the waveguide core **114**. The bottom layer **202** can include both a first portion **204** and a second portion **206**. The bottom layer can include a hybrid material, such as Rh/Au, Ir/Au, or Pt/Au, for example. For instance, the first portion **204** can include Rh and the second portion **206** can include Au. The write head **200** can further include a top layer **108** comprising Rh and disposed adjacent to the heat sink **106**.

[0063] In many cases, a TAMR NFT structure (e.g., structure **100** in FIG. 1) can comprise an Au-only PBL. The PBL can recess from the ABS at a high temperature during TAMR recording. The hybrid PBL configuration as described herein can overcome the deficiencies of many PBL structures by utilizing multiple materials in the PBL. The PBL can include a low optical loss but less thermo-mechanically stable material, such as Au, in the cooler region away from the ABS, and a thermo-mechanically stable material such as Rh or Ir in the hotter region near the ABS. Such a combination can provide higher reliability while maintaining similar optical conversion efficiency from the waveguide mode to the surface plasmon mode at the PBL.

[0064] FIGS. 3A-3B illustrate three-dimensional half-model views **300A-B** of a PBL layer. In many cases, a PBL **110** can include Au, as is shown in FIG. 3A. In these cases, the Au of the PPG bottom layer (PBL) may be recessed only around 30 nm from the ABS **106**. The PBL may be close to the peg, which can include a hot spot in the head during writing. Further, in the high temperature environment, recession of the PBL from the ABS can be observed.

[0065] In FIG. 3B, the PBL **202** can include a hybrid PBL comprising Au (e.g., **204A**) and Rh (e.g., **204B**). A planar plasmon generator (PPG) and the peg can be disposed near the ABS **106**. For example, the PBL can include a first portion **206** (e.g., comprising Au) and a second portion **204** (e.g., comprising Rh). The PBL **202** in FIG. 3B can move the Au portion away from the high temperature region near the ABS to a lower temperature region away from the ABS.

[0066] FIGS. 4A-4B illustrate cross-sectional views **400A-B** of a PBL. As shown in FIG. 4A, the PBL can include an Au portion **110**. A BSDh **404** can define a thickness of a dielectric film **406** in front of the Au portion **110**.

[0067] FIG. 4B illustrates a hybrid PBL. The hybrid PBL can include an Au portion **206** and a Rh portion **208** connected to the Au portion **206**. The Rh portion **204** can be disposed near the ABS. PBLh2 **410** defines the recession of the Au portion **206** from the ABS. The maximum Au temperature at location **412** is lower in the hybrid PBL than in the PBL structure of FIG. 4A.

[0068] FIGS. 5A-5D provide graphical illustrations of the comparison of a single material PBL (FIG. 4A) and a hybrid PBL (FIG. 4B). In the case of the hybrid PBL, PBLh2 is varied while BSDh is held at 30 nm. In case of single material PBL, BSDh is varied. The figures represent metrics at

optimized laser currents (I_{eff}) at 650 kilo track per inch KTPI (including a 10% margin).

[0069] FIG. 5A is a graphical representation **500a** of a normalized areal density capability (ADC) for varying values of the BSDh for the single material PBL structure and PBLh2 for the hybrid PBL structure. As shown in FIG. 5A, a first series of points **502a**, **502b** can include values for a BSDh with a first trendline **504** specifying a trend of values. Further, a second series of points **506a**, **506b** can include values for a PBLh2 with a second trendline **508** specifying a trend of values. FIG. 5A illustrates an ADC for a write head as described herein to the ADC of a write head of many cases. Replacing the front of the PBL by Rh can lead to a gradual degradation of the ADC of the hybrid PBL. At the target value of PBLh2=110 nm, (i.e., 80 nm Rh in front of the PBL), the ADC can be about 3% lower than the one in many cases, such as the PBL as shown in FIGS. 1A-B (e.g., a PBL structure). This slight degradation can be caused by the absorption of the surface plasmon in the Rh part while it travels along the PBL towards the ABS.

[0070] FIG. 5B is a graphical representation **500b** of a peg temperature at a recording point for varying values of the BSDh and PBLh2. As shown in FIG. 5B, a first series of points **510a**, **510b** can include values for a BSDh with a first trendline **512** specifying a trend of values. Further, a second series of points **514a**, **514b** can include values for a PBLh2 with a second trendline **516** specifying a trend of values. The peg temperature can include an increase of around 5.9% for the hybrid PBL structure vs. the PBL structure at the target value of PBLh2=110 nm.

[0071] FIG. 5C is a graphical representation **500c** of a laser current (I_{eff}) at a for varying values of the BSDh and PBLh2. As shown in FIG. 5C, a first series of points **518a**, **518b** can include values for a BSDh with a first trendline **520** specifying a trend of values. Further, a second series of points **522a**, **522b** can include values for a PBLh2 with a second trendline **524** specifying a trend of values. As shown in FIG. 5C, a laser current for a hybrid PBL structure can be 9.4% higher than that of the PBL structure at the target value of PBLh2=110 nm.

[0072] FIG. 5D is a graphical representation **500d** of an Au temperature at a recording point for varying values of the BSDh and PBLh2. As shown in FIG. 5D, a first series of points **526a**, **526b** can include values for a BSDh with a first trendline **528** specifying a trend of values. Further, a second series of points **530a**, **530b** can include values for a PBLh2 with a second trendline **532** specifying a trend of values. As shown in FIG. 5D, an Au temperature in the hybrid PBL structure can drop by 27% compared to that in the PBL structure at the target value of PBLh2=110 nm.

[0073] A similar Au temperature can be achieved if the BSDh is set to around 140 nm, which may result in too great of a peg temperature, a high I_{eff}, and a large ADC loss.

[0074] The graphical illustrations in FIGS. 5A-5D can illustrate changes to other write heads (e.g., write heads implementing PBL structure), if the Au-PBL recesses from the ABS, which can be equivalent to an increase in BSDh. For example, the observed peg temperature increase of the hybrid PBL structure can already be reached when the BSDh in the many write heads increases by less than 10 nm.

[0075] FIG. 6A is a cross-section view of a NFT **600a** with an alumina layer **602** deposited on top of a waveguide **604**. As shown in FIG. 6A, an alumina layer **602** can be disposed on top of a waveguide **604** via a deposition process (e.g., atomic layer deposition (ALD)). In some instances, the alumina layer **602** can be deposited after a WyG CMP process. FIG. 6B is a top view of a NFT **600b** with an alumina layer **602** deposited on top of a waveguide. From the top view, the alumina layer **602** can be seen.

[0076] FIG. 7A is a cross-section view of a NFT **700a** with an alumina layer after an IBE etching of the alumina layer. As shown in FIG. 7A, the alumina layer **702** can be etched using an ion beam etching (IBE) etching process. The etching process can define an etched portion **706** in the alumina layer **702**.

[0077] In some instances, a photo resist (PR) can be coated on part of the alumina layer, which can define a shape of the opening. The IBE etching process can remove film not protected by a mask. A resist mask can be stripped, and a wall angle of the etched portion of the alumina layer can vary

between 0 degrees and 60 degrees.

[0078] FIG. 7B is a top view of a NFT **700b** with an alumina layer after an IBE etching of the alumina layer. As shown in FIG. 7B, the top view shows the alumina layer **702** as well as the etched portion **706** etched within the alumina layer.

[0079] FIG. 8A is a cross-section view of a NFT **800a** with a full film deposition on top of the alumina layer. As shown in FIG. 8A, a film **808** can be added on top of the alumina layer **802**. The film can include a Rh film. FIG. 8B is a top view of a NFT **800b** with a full film deposition on top of the alumina layer. As shown in FIG. 8B, the film **808** can include the top layer of the NFT **800b** including in the etched portion **806**.

[0080] FIG. 9A is a cross-section view of an NFT **900a** after a field Rh removal and CMP/IBE. As shown in FIG. 9A, the etched portion **906** can be filled with the full film Rh after the full film (e.g., in FIG. 8A) is removed from a remainder of the top portion of the NFT **900a**. The filled etched portion **902** can result in a flat surface along the alumina layer **902** with the alumina deposition, chemical mechanical polishing/planarization (CMP), and/or IBE etching. FIG. 9B is a top view of an NFT **900b** after a field Rh removal and CMP/IBE. As shown in FIG. 9B, the alumina layer **902** can be seen as the top layer. Further, the etched portion **906** can include the film (e.g., film **808** as shown in FIG. 8A).

[0081] FIG. 10A is a cross-section view of an NFT **1000a** with a photoresist being patterned to define a final Rh length. As shown in FIG. 10A, a photoresist layer **1012** can be coated on a portion of the alumina layer **1002**. The photoresist **1012** can define a final position of Rh layer. In some instances, the portion of the alumina layer including the etched portion **1006** may not include the photoresist **1012**, thereby exposing the etched portion **1006** comprising the film (e.g., film **808**). FIG. 10B is a top view of an NFT **1000b** with a photoresist being patterned to define a final Rh length. As shown in FIG. 10B, the photoresist **1012** can comprise a top layer, with the film in the etched portion **1006** being exposed as part of the top layer.

[0082] FIG. 11A is a cross-section view of an NFT **1100a** with the IBE process applied to pattern the Rh and the photoresist being stripped. As shown in FIG. 11A, the photoresist (e.g., **1012**) can be removed, and a portion of the film (e.g., **808**) can be removed from the etched portion **1106** such that only a portion of the film **1108** remains in the etched portion **1106**. An etching process (e.g., IBE) can be applied to remove the Rh film not protected by a mask. The resist mask can then be stripped. The Rh wall angle can be varied between 10 degrees and 60 degrees.

[0083] FIG. 11B is a top view of an NFT **1100b** with the IBE process applied to pattern the Rh and the photoresist being stripped. As shown in FIG. 11B, the alumina layer **1102** can include a top layer for a portion of the NFT **1100b**. The etched portion **1106** can include a first portion exposing the alumina layer **1102** and a second portion exposing the remaining film (e.g., **808**) **1108**.

[0084] FIG. 12A is a cross-section view of an NFT **1200a** with a full film Au layer being deposited on top of the alumina layer. The full film Au layer **1208** can be deposited across an entirety of the alumina layer **1202** including the etched portion **1206**. FIG. 12B is a top view of an NFT **1200b** with a full film Au layer being deposited on top of the alumina layer. As shown in FIG. 12B, the Au layer **1208** can be disposed across the top portion of the NFT **1200b**.

[0085] FIG. 13A is a cross-section view of an NFT **1300a** after the Au layer is removed. As shown in FIG. 13A, the full Au layer (e.g., **1208**) can be removed and a CMP/IBE process can be implemented to achieve a flat surface. For instance, the etched portion **1306** include a portion **1310** comprising a remaining part of the Au layer (e.g., **1208**) and a second portion **1308** comprising the film (e.g., **808**). The Au layer can be removed by an SiO₂ deposition, CMP, and/or IBE, for example.

[0086] FIG. 13B is a top view of an NFT **1300b** after the Au layer is removed. As shown in FIG. 13B, at least a portion of the top surface can include the alumina layer **1302**. Further, the etched portion **1306** can include a first portion **1310** comprising the Au layer and a second portion **1308** comprising the film.

[0087] FIG. **14A** is a cross-section view of an NFT **1400a** with a full film Rh deposition. As shown in FIG. **14A**, the Rh layer **1412** can be disposed above the alumina layer **1402** and the etched portion **1406**. The Rh layer **1412** can comprise a flat surface. FIG. **14B** is a top view of an NFT **1400b** with a full film Rh deposition. As shown in FIG. **14B**, an entirety of the top layer can include the Rh layer **1412**.

[0088] FIG. **15A** is a cross-section view of an NFT **1500a** with a photolithography patterning process applied. As shown in FIG. **15A**, a peg patterning mask **1514** can be disposed above the Rh layer **1512**. A photolithography patterning process can be used to apply the peg patterning mask **1514**. After this process, the final NFT shape can be defined by the mask design as provided in the peg patterning mask **1514**.

[0089] FIG. **15B** is a top view of an NFT **1500b** with a photolithography patterning process applied. As shown in FIG. **15B**, the peg patterning mask **1514** can provide a design for the NFT. The peg patterning mask **1514** can be disposed above the Rh layer **1512**.

[0090] FIG. **16A** is a cross-section view of an NFT **1600a** after an etching process being applied to remove a portion of the Rh layer. As shown in FIG. **16A**, portions of the Rh layer **1612** can be removed. After the etching process, the region of the film below the mask (e.g., **1612**) can be left to provide the design of the mask. At least a portion of the alumina layer **1602** may not be protected by the mask. The mask can be removed after a dry etching patterning process is performed.

[0091] FIG. **16B** is a top view of an NFT after an etching process being applied to remove a portion of the Rh layer. As shown in FIG. **16B**, the alumina layer **1602** can be exposed at the top layer. Further, a portion of the Rh layer **1612** previously below the peg patterning mask (e.g., **1514**) can be exposed in a design provided by the mask.

[0092] FIG. **17A** is a cross-section view of an NFT **1700a** with a cladding material added. As shown in FIG. **17A**, a cladding material **1716** can be added above the alumina layer **1702** to provide a flat surface at the top layer. The cladding material **1716** can include an ALD or a PECVD SiO₂ material. The cladding material deposition can be performed after a CMP planarization process to finish the NFT fabrication process. As shown in FIG. **17A**, the cladding material **1716** can be disposed around the Rh layer **1712** at a top layer of the NFT **1700a**.

[0093] FIG. **17B** is a top view of an NFT **1700b** with a cladding material added. As shown in FIG. **17B**, at least a portion of the top layer can include the cladding material **1716**. The top layer can further include the portion of the remaining Rh layer **1712** as designed by the mask. In embodiments, the cladding layers are made of Al₂O₃ or SiO₂, for example.

[0094] In a first example embodiment, a thermally-assisted magnetic recording (TAMR) write head is provided. The TAMR write head can include a main pole (e.g., **102**). The main pole can include a tip portion disposed adjacent to an air-bearing surface (ABS). The ABS can include a surface adjacent to a disk (e.g., disk **103**). The main pole can be configured to direct a magnetic field toward a magnetic recording medium to interact with the magnetic recording medium (e.g., to write to the disk). The TAMR head can further include a heat sink (e.g., **104**) disposed adjacent to the main pole.

[0095] The TAMR head can further include a near field transducer (NFT). The NFT can include a first layer (e.g., **108**) and a second layer (e.g., **202**). The first layer (e.g., **108**) can include a first plasmonic material (e.g., a robust, but still mildly plasmonic material such as rhodium, iridium, platinum). Further, the first layer can be disposed adjacent to the heat sink.

[0096] In some instances, a plasmonic material that is “mild” or “good” can be defined by a plasmon quality factor (PQF). The PQF can be defined as a ratio given by the real part of the dielectric function divided by the imaginary part of the dielectric function. A more negative PQF can specify a better plasmonic material. Materials with a PQF around -1 are considered mildly plasmonic while materials with a PQF around -10 and smaller are considered good plasmonic materials. “Robust” or “thermally stable” plasmonic materials can be specified by the melting temperature of the materials. A higher melting temperature can define a more robust material.

[0097] The second layer (e.g., **202**) can include a portion of a second plasmonic material (e.g., a good plasmonic metallic material such as gold) and a first plasmonic portion (e.g., a robust, but still mildly plasmonic material such as rhodium). The second plasmonic portion of the second layer can be disposed adjacent to the ABS.

[0098] In some instances, the NFT can include an alumina layer (e.g., **112**) disposed between the waveguide and the second layer of the near field transducer. The alumina layer can include an etched recess recessed into the alumina layer. The etched recess can be etched into the alumina layer via an etching process (e.g., IBE).

[0099] The second layer can be disposed within the etched recess in the alumina layer. The robust metallic material can be deposited in the etched recess responsive to a removal of a robust metallic material film disposed over the alumina layer. A second portion of the etched recess can include the second plasmonic portion of the second layer. Further, the second plasmonic portion can be deposited in the etched recess responsive to a removal of a second plasmonic material film disposed over the alumina layer.

[0100] The TAMR head can further include a waveguide (e.g., **114**) configured to direct a laser light source (e.g., generated from a laser (not shown)) to heat a portion of the magnetic recording medium.

[0101] In some instances, the first layer can be defined by a patterning mask added above the first layer. For instance, a portion of the first layer can be removed according to the patterning mask. The patterning mask can be removed, and the patterning mask can define a final shape of the near field transducer.

[0102] In another example embodiment, a method for manufacturing a near field transducer that is part of a thermally-assisted magnetic recording (TAMR) write head is provided. The method can include disposing an alumina layer above a waveguide. For example, in FIG. 6A, an alumina layer **602** can be disposed above a waveguide **604**.

[0103] The method can further include forming an etched recess in the alumina layer via an etching process. For example, an etched recess **706** can be formed in the alumina layer **702**, as shown in FIG. 7A. In some instances, the etching process comprises an ion beam etching (IBE) etching process.

[0104] The method can further include disposing a first plasmonic material in a first portion of the etched recess. For example, as shown in FIG. 8A, a full film of the first plasmonic material (e.g., film **808**) can be disposed above the alumina layer. Further, as shown in FIG. 9A, a portion of the film (e.g., **808**) can be removed such that only the robust material remains in the etched recess (e.g., Rh material included in etched recess **906**).

[0105] In some instances, the method can further include disposing a photo-resist layer (e.g., **1012** as shown in FIG. 10A) above the alumina layer. The photo-resist layer can define a length of the first layer. Further, the photo-resist layer can be removed, where the removing of the photo-resist layer removes part of the first plasmonic material remaining in the etched recess to expose the second portion of the etched recess. For example, it is shown in etched recess **1106** in FIG. 11A, where only a portion of the Rh film **1108** remains in the etched recess **1106** and a remaining portion of the etched recess is exposed.

[0106] The method can further include disposing a second plasmonic material in a second portion of the etched recess. The first plasmonic material and the second plasmonic material comprise a second layer of the near field transducer. For example, as shown in FIG. 12A, a full film of the second plasmonic material **1208** can be disposed above the alumina layer **1202**. Further, a portion of the full film of the second plasmonic material can be removed such that the second plasmonic material remains only in the second portion of the etched recess. For instance, as shown in FIG. 13A, the Au film **1310** can remain in the second portion of the etched recess **1306**.

[0107] The method can further include disposing a first layer comprising the first plasmonic material above the alumina layer and the etched recess. For example, in FIG. 14A, the Rh layer

1406 can be disposed above the alumina layer and the etched recess.

[0108] In some embodiments, a patterning mask (e.g., **1514** in FIG. **15A**) can be disposed above the first layer. The patterning mask can define a final shape of the near field transducer. Further, a portion of the first layer not below the patterning mask can be removed (e.g., as shown in FIG. **16A**).

[0109] Further, in some embodiments, the method can include disposing a cladding material adjacent to the first layer such that the first layer and the cladding material form a flat surface. For example, cladding material **1716** can be disposed around the portion of the first layer that was removed such that a top surface of the NFT can be flat.

[0110] In another example embodiment, a near field transducer (NFT) is provided. The NFT can include a first layer comprising a first plasmonic material (e.g., rhodium, iridium, platinum). The first layer can be disposed adjacent to the heat sink. In some instances, the first layer is defined by a patterning mask added above the first layer. The patterning mask can define a final shape of the near field transducer.

[0111] The NFT can also include a second layer that can include a second plasmonic portion (e.g., comprising gold) and a first plasmonic portion (e.g., comprising rhodium, iridium, or platinum). The first plasmonic portion can be disposed adjacent to the ABS. The NFT can further include a waveguide.

[0112] In some instances, the NFT can include an alumina layer disposed between the waveguide and the second layer of the near field transducer. The alumina layer can include an etched recess formed into the alumina layer via an etching process. The second layer can be disposed within the etched recess.

[0113] It will be understood that terms such as “top,” “bottom,” “above,” “below,” and x-direction, y-direction, and z-direction as used herein as terms of convenience that denote the spatial relationships of parts relative to each other rather than to any specific spatial or gravitational orientation. Thus, the terms are intended to encompass an assembly of component parts regardless of whether the assembly is oriented in the particular orientation shown in the drawings and described in the specification, upside down from that orientation, or any other rotational variation.

[0114] It will be appreciated that the term “present invention” as used herein should not be construed to mean that only a single invention having a single essential element or group of elements is presented. Similarly, it will also be appreciated that the term “present invention” encompasses a number of separate innovations, which can each be considered separate inventions. Although the present invention has been described in detail with regards to the preferred embodiments and drawings thereof, it should be apparent to those skilled in the art that various adaptations and modifications of embodiments of the present invention may be accomplished without departing from the spirit and the scope of the invention. Accordingly, it is to be understood that the detailed description and the accompanying drawings as set forth hereinabove are not intended to limit the breadth of the present invention, which should be inferred only from the following claims and their appropriately construed legal equivalents.

Claims

1. A method for manufacturing a thermally-assisted magnetic recording (TAMR) write head, the method comprising: disposing a heat sink adjacent to a main pole, the main pole including a tip portion disposed adjacent to an air-bearing surface (ABS), the main pole configured to direct a magnetic field toward a magnetic recording medium to interact with the magnetic recording medium; disposing a first layer of a near-field transducer (NFT) adjacent to the heat sink, the first layer comprising a first plasmonic material; disposing a second layer of the NFT adjacent to the first layer, the second layer including a second plasmonic portion and a first plasmonic portion; and disposing a waveguide adjacent to the NFT, the waveguide configured to direct a laser light source

to heat a portion of the magnetic recording medium.

2. The method of claim 1, further comprising: disposing an alumina disposed between the waveguide and the second layer of the near field transducer, wherein the alumina layer comprises an etched recess recessed into the alumina layer.

3. The method of claim 1, wherein the first plasmonic portion comprises any of rhodium, iridium, or platinum, and wherein the second plasmonic portion comprises gold.

4. The method of claim 1, wherein the first portion of the second layer is disposed adjacent to the ABS.

5. The method of claim 1, wherein the etched recess is etched into the alumina layer via an etching process.

6. The method of claim 5, wherein a first portion of the etched recess includes the first plasmonic material of the second layer, wherein the first plasmonic material is deposited in the etched recess responsive to a removal of a first plasmonic material film disposed over the alumina layer.

7. The method of claim 5, wherein a second portion of the etched recess includes the second plasmonic portion of the second layer, wherein the second plasmonic portion is deposited in the etched recess responsive to a removal of a second plasmonic material film disposed over the alumina layer.

8. The method of claim 7, wherein the first layer is defined by a patterning mask added above the first layer, wherein a portion of the first layer is removed according to the patterning mask, and wherein the patterning mask is removed, the patterning mask defining a final shape of the near field transducer.

9. A method for manufacturing a near field transducer that is part of a thermally-assisted magnetic recording (TAMR) write head, the method comprising: disposing an alumina layer above a waveguide; disposing a first plasmonic material in a first portion of the etched recess; disposing a second plasmonic material in a second portion of the etched recess, wherein the first plasmonic material and the second plasmonic material comprise a second layer of the near field transducer; and disposing a first layer comprising the first plasmonic material above the alumina layer and the etched recess.

10. The method of claim 9, further comprising: forming an etched recess in the alumina layer via an etching process.

11. The method of claim 10, wherein the etching process comprises an ion beam etching (IBE) etching process.

12. The method of claim 10, further comprising: disposing a full film of the first plasmonic material above the alumina layer; and removing a portion of the full film of the first plasmonic material such that only the first plasmonic material remains in the etched recess.

13. The method of claim 12, further comprising: disposing a photo-resist layer above the alumina layer, the photo-resist layer defining a length of the first layer; and removing the photo-resist layer, wherein the removing of the photo-resist layer removes part of the first plasmonic material remaining in the etched recess to expose the second portion of the etched recess.

14. The method of claim 12, further comprising: disposing a full film of the second plasmonic material above the alumina layer; and removing a portion of the full film of the second plasmonic material such that the second plasmonic material remains only in the second portion of the etched recess.

15. The method of claim 14, further comprising: disposing a patterning mask above the first layer, the patterning mask defining a final shape of the near field transducer; and removing a portion of the first layer not below the patterning mask.

16. The method of claim 15, further comprising: disposing a cladding material adjacent to the first layer such that the first layer and the cladding material form a flat surface.

17. A method comprising: disposing a first layer comprising a first plasmonic material adjacent to a heat sink; disposing a second layer including a second plasmonic portion and a first plasmonic

portion adjacent to the first layer, the first plasmonic portion disposed adjacent to an air-bearing surface (ABS); disposing an alumina layer disposed between a waveguide and the second layer.

18. The method of claim 17, wherein the alumina layer comprises an etched recess recessed into the alumina layer.

19. The method of claim 18, wherein the second layer is disposed within the etched recess.

20. The method of claim 17, wherein the first layer is defined by a patterning mask added above the first layer, the patterning mask defining a final shape of the near field transducer.
