

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250276371

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

Nelson; Scott et al.

ALIGNMENT MONITORING AND CONTROL

Abstract

An additive manufacturing system includes an energy delivery device configured to deliver energy to a build surface of an additively-manufactured component to form a melt pool and a powder delivery device configured to direct a powder stream toward the melt pool. The system further includes a powder flow monitoring system configured to observe the powder stream and an optical system configured to observe the melt pool. A computing device configured to receive data indicative of a position of the powder stream, and receive data indicative of a position of the melt pool. The computing device is configured to determine a relative position of the powder stream to the melt pool and control, based on the determined relative position of the powder stream to the melt pool, one or both of the powder delivery device and the energy delivery device.

Inventors: Nelson; Scott (Indianapolis, IN), Puhl; David James (Indianapolis, IN), Grafton-Reed; Clive (London, GB), Daum; Peter E. (Indianapolis, IN), Proctor; Robert F. (Indianapolis, IN), Heason; Christopher Paul (London, GB)

Applicant: Rolls-Royce Corporation (Indianapolis, IN); Rolls-Royce plc (London, GB)

Family ID: 96881593

Appl. No.: 18/593538

Filed: March 01, 2024

Publication Classification

Int. Cl.: B22F10/37 (20210101); B22F10/28 (20210101); B22F12/90 (20210101); B23K26/342 (20140101); B33Y10/00 (20150101); B33Y30/00 (20150101); B33Y50/02 (20150101)

U.S. Cl.:

CPC B22F10/37 (20210101); B22F10/28 (20210101); B22F12/90 (20210101); B23K26/342 (20151001); B33Y10/00 (20141201); B33Y30/00 (20141201); B33Y50/02 (20141201);

Background/Summary

TECHNICAL FIELD

[0001] The disclosure relates to additive manufacturing techniques.

BACKGROUND

[0002] Additive manufacturing generates three-dimensional structures through addition of material layer-by-layer or volume-by-volume to form the structure, rather than removing material from an existing component to generate the three-dimensional structure. Additive manufacturing may be advantageous in many situations, such as rapid prototyping, forming components with complex three-dimensional structures, or the like. In some examples, additive manufacturing may utilize powdered materials and may melt or sinter the powdered material together in predetermined shapes to form the three-dimensional structures.

SUMMARY

[0003] Additive manufacturing systems and techniques, such as directed energy deposition (DED) processes, operate by depositing material layer-by-layer to form an additively-manufactured component (hereinafter, “component”). In such processes, material is deposited by a powder delivery device directing a powder stream toward a melt pool formed on a build surface of the component by energy from an energy delivery device. The melt pool and added powder then solidify as an added layer. The added layer may become the new build surface for subsequent layers. Among other factors, alignment between a relative position of the powder stream to the melt pool may be important to the quality and efficiency of the additive manufacturing process. For example, if the powder stream is not in alignment with the melt pool, material in the powder stream may miss the melt pool or may be added to one portion of the melt pool at a greater rate than material added to another portion of the melt pool, resulting in reduced mass capture efficiency or asymmetric mass capture of powder by the melt pool. In such an unaligned state, underbuild, overbuild, or other problems may occur, leading to a build that is out of specification and ultimately discarding or reworking the component. Additive manufacturing systems of the present disclosure may address these and other problems by determining a relative position of the powder stream to the melt pool. In response to determining that the powder stream is not in alignment with the melt pool, a computing device of the additive manufacturing system may adjust the relative position of the powder stream to the melt pool. For instance, the computing device may adjust the position or settings of the powder delivery device, the energy delivery device, or both (e.g., to improve alignment of the powder stream and the melt pool). In this way, alignment between the powder stream and melt pool may be monitored and controlled, in-situ, during the additive manufacturing process. Such monitoring and control may desirably result in improved mass capture by the melt pool and a quality and efficient build.

[0004] An example additive manufacturing system includes an energy delivery device configured to deliver energy to a build surface of an additively-manufactured component to form a melt pool in the build surface of the component and a powder delivery device configured to direct a powder stream toward the melt pool. The system includes a powder flow monitoring system configured to observe the powder stream and an optical system configured to observe the melt pool. The system also includes a computing device configured to receive data indicative of a position of the powder stream from the powder flow monitoring system and receive data indicative of a position of the melt pool from the optical system. The computing system is configured to determine, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool, and control, based on the determined relative position of the powder stream to the melt pool, the powder delivery device and the energy delivery device.

[0005] An example method includes delivering, via an energy delivery device, energy to a build

surface of an additively-manufactured component to form a melt pool in the build surface of the component and receiving, from an optical system, data indicative of a position of the melt pool. The technique includes delivering, via a powder delivery device, a powder stream to the melt pool to add material to the component and receiving, from a powder flow monitoring device, data indicative of a position of the powder stream. The technique includes determining, via a computing device, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool. The technique includes controlling, via the computing device, the energy delivery device or the powder delivery device.

[0006] The details of one or more examples are set forth in the accompanying drawings and the description below. Other features, objects, and advantages will be apparent from the description and drawings, and from the claims.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0007] FIG. 1 is a conceptual block diagram illustrating aspects of an example additive manufacturing system that includes a powder delivery device configured to direct a powder stream toward a melt pool formed by an energy delivery device.

[0008] FIG. 2 is a conceptual and schematic diagram illustrating further aspects of the additive manufacturing system of FIG. 1.

[0009] FIG. 3 is a conceptual diagram illustrating an example of portions of a powder stream imaged by a powder flow monitoring system.

[0010] FIG. 4 is an example calibration curve of particle detections versus mass flow.

[0011] FIG. 5 is a conceptual block diagram illustrating portions of the example additive manufacturing system of FIG. 1, including an optical system for observing thermal emissions around a melt pool and a thermal camera for monitoring a size of the melt pool.

[0012] FIG. 6 is a conceptual block diagram illustrating an example optical system for observing a melt pool formed during the additive manufacturing technique.

[0013] FIG. 7 is a process flow diagram illustrating a mass flux monitoring, heat flux monitoring, and alignment monitoring and control technique.

[0014] FIG. 8 is a conceptual and schematic diagram illustrating operation of a deposition head during an additive manufacturing process.

[0015] FIG. 9 is a conceptual and schematic diagram illustrating the deposition head of FIG. 8 in a misaligned state.

[0016] FIG. 10 is a conceptual and schematic diagram illustrating the deposition head of FIG. 8 under a control technique to align a powder stream and melt pool.

[0017] FIG. 11 is a conceptual and schematic diagram illustrating the deposition head of FIG. 8 under another control technique to align the powder stream and melt pool.

[0018] FIG. 12 is a flow diagram illustrating an example technique according to the present disclosure.

[0019] FIG. 13 is a flow diagram illustrating an example technique according to the present disclosure.

DETAILED DESCRIPTION

[0020] The disclosure generally describes techniques and systems for managing residual stresses during an additive manufacturing technique, such as a directed energy deposition (DED) technique. During DED additive manufacturing, a component is built up by adding material to the component in sequential layers. The final component is composed of a plurality of layers of material. In some blown powder additive manufacturing techniques for forming components from metals, ceramics, and/or alloys, an energy source may direct energy at a substrate to form a melt pool. A powder

delivery device may deliver a powder to the melt pool, where at least some of the powder at least partially melts and is joined to the melt pool and, thus, the substrate. In some examples, the powder delivery device and the energy delivery device may be part of a common deposition head configured to deliver both powder and energy to the build surface.

[0021] The properties of the final component, including the presence or absence of material defects (e.g., pores or void spaces, material not joined to adjacent material, and the like), and the efficiency with which material is added to the component, may be a function of the interaction between the powder stream and the melt pool. As such, measurement, modeling, control, and validation of the position of the powder stream from the powder delivery device and the melt pool formed by the energy delivery device of a blown powder additive manufacturing system (e.g., a DED system) may enable characterization or prediction of final component properties, control of the additive manufacturing technique during the process, quality assurance for the final component, development of new additive manufacturing techniques, and the like.

[0022] Challenges may arise while performing additive manufacturing techniques with additive manufacturing systems. For example, the powder stream and the melt pool may be out of alignment. The relative position of the powder stream to the melt pool may be considered out of alignment when the powder in the powder stream misses the melt pool or is added preferentially to only a portion of the melt pool. The system may become misaligned for many reasons, including one or more of a manufacturing error, an operator setup error, wear and tear on the system, bumps or jostles during an additive manufacturing process, or the like. Furthermore, some operations of the additive manufacturing system may cause, even temporarily, misalignment of the relative position of the powder stream to the melt pool. For example, a travel speed of a deposition head exceeding a certain threshold may cause powder to powder to displace from a central axis of the powder delivery device during flight across a working distance to the build surface, causing the powder stream to slightly trail behind the melt pool as the deposition head travels along a toolpath to deposit a layer. Similarly, in some examples, such as when a component with complex geometry is being fabricated and the powder stream is not coincident with the force of gravity, the gravitational force may act on the powder stream to displace the powder stream from the central axis of the powder delivery device, causing the relative position of the powder stream to the melt pool, at the build surface, to be different than the desired relative position of the powder stream to the melt pool.

[0023] Misalignment in the relative position of the powder stream to the melt pool at the build surface may cause one or more problems with the additive manufacturing process and the resulting component. For example, powder intended to be deposited on the component may miss the melt pool, causing reduced capture efficiency, wasted material, reduced layer thickness, and/or increased manufacturing time. Additionally, even when captured by the melt pool, the misaligned powder stream may be added preferentially to only a portion of the melt pool, which may cause underbuild (e.g., less material deposited than desired) in some portions of the layer and overbuild (e.g., more material deposited than desired) in other portions. Other asymmetric deposition behavior may be observed, depending on the travel direction.

[0024] In accordance with one or more examples of the current disclosure, additive manufacturing systems and techniques may address these and other problems. Additive manufacturing systems according to the present disclosure may include an energy delivery device configured to deliver energy to a build surface of an additively-manufactured component to form a melt pool in the build surface of the component and a powder delivery device configured to direct a powder stream toward the melt pool. The system may include a powder flow monitoring system configured to observe the powder stream and an optical system configured to observe the melt pool. The system may also include a computing device. The computing device may receive, from the powder flow monitoring system, data indicative of a position of the powder stream from the powder flow monitoring system, and receive, from the optical system, data indicative of a position of the melt

pool. The computing device may determine, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool. The computing device may control, based on the determined relative position of the powder stream to the melt pool, the powder delivery device and the energy delivery device. In this way alignment between the powder stream and the melt pool may be monitored and controlled to improve the mass capture efficiency and quality of the additive manufacturing process and/or resulting component.

[0025] In some examples, to determine the position of the powder stream, the computing device may determine a position of a central axis of the powder stream, and to determine the position of the melt pool, the computing device may determine a position of a center point of the melt pool. The computing device may compare the position of the central axis of the powder stream to the position of the center point of the melt pool. Upon determination that a distance between the position of the central axis of the powder stream does not exceed a threshold distance, the computing device may determine that the additive manufacturing process may continue based on the validated relative position of the powder stream to the melt pool. Upon a determination that the distance between the central axis of the powder stream and the center point of the melt pool exceeds the threshold distance, the computing device may adjust the relative position of powder stream to the melt pool by adjusting the position or settings of the powder delivery device, the energy delivery device, or both to decrease the distance between position of the central axis of the powder stream to the center of the melt pool. In some examples, the computing device may adjust the relative position of the powder stream to the melt pool such that the central axis of the powder stream intersects the center point of the melt pool. Accordingly, powder of the powder stream may be delivered directly to the melt pool, symmetrically delivering powder to each portion of the melt pool evenly. In this way, additive manufacturing systems according to the present disclosure may monitor, control, and maintain alignment of the powder stream and the melt pool.

[0026] In some examples, the computing device may determine a capture efficiency of powder in the powder stream by the melt pool. For example, the computing device may compare the mass of powder delivered by a powder source through the powder delivery device to a mass of powder captured by the melt pool that is sensed by a topology sensor. In some examples, the computing device may adjust the relative position of the powder stream to the melt pool to increase the capture efficiency. For example, the computing device may store and execute a machine learning algorithm trained on the determined capture efficiency and the relative position of the powder stream to the melt pool, and adjust the powder delivery device and/or the energy delivery device based on output from the machine learning algorithm. The capture efficiency of the melt pool may thus be optimized and equalized, which may yield higher efficiency (e.g., reduced material waste, reduced layers to deposit a certain volume) and/or more uniform (e.g., more symmetric build) additively-manufactured components.

[0027] Although not necessary, in some examples the powder delivery device and the energy delivery device may be parts of a common deposition head. The deposition head may travel along a toolpath to deposit a layer of material during the build. The position of the powder delivery device and the position of the energy delivery device may each be independently controllable, which may allow for control of the relative position of the powder stream to the melt pool during manufacturing. For example, the energy delivery device may include a laser which delivers an energy beam through a portion of the deposition head. The laser may be mechanically supported one or more adjustable support members. The adjustable support members may allow for independent adjustment of the energy delivery device in the x, y, and/or z-directions relative to the remainder of the deposition head (e.g., the powder delivery device), which may allow for changing the position and/or size of the melt pool relative to the powder stream. Additionally, or alternatively, the energy delivery device may include one or more galvanometers or other mirror and/or lens systems. The position of the melt pool may be adjusted by manipulation of the one or more galvanometers.

[0028] In examples where the powder delivery device and the energy delivery device are parts of a common deposition head, the powder delivery device may direct the powder stream to the melt pool through one or more delivery nozzles at the downstream end of the deposition head. The position and/or angle of the one or more delivery nozzles may be manipulated by the computing device, which may allow for independent adjustment of the powder stream. In this way, the relative position of the powder stream to the melt pool may be adjusted.

[0029] In some examples, the computing device may adjust the relative position of the powder stream to the melt pool to account for forces acting on the powder stream as the powder travels across a working distance between the powder delivery device and the melt pool. For example, the powder stream central axis may be defined at the downstream end of the deposition head, and the powder stream may displace from the powder stream central axis when traveling across the working distance, such that the powder stream is displaced from the powder stream central axis by a displacement distance when the powder stream reaches the melt pool. For example, the travel speed of the deposition head along the toolpath may cause the displacement of the powder stream from the powder stream central axis. Additionally, or alternatively, the powder delivery device may direct the powder stream to the build surface at an angle with respect to gravity, and the powder stream may displace from the powder stream central axis due to the gravitational force.

[0030] The computing device may account for displacement distance of the powder stream due to the speed of the deposition head and/or the gravitational force by adjusting the relative position of the powder stream to the melt pool. For example, the powder stream central axis, which may be defined at a downstream end of the deposition head, may be positioned ahead of the melt pool along the toolpath, which may be called a leading position. The powder stream may displace from the powder stream central axis along the toolpath as the powder travels across the working distance between the deposition head and the build surface. Since in such examples the position of the melt pool may slightly trail behind the powder stream central axis along the toolpath, the powder in the powder stream may land in the melt pool. Since the displacement distance may be a function of the travel speed of the deposition head along the toolpath, in some examples the computing device may increase the amount by which the powder stream central axis leads the melt pool in response to an increase in travel speed of the deposition head. In this way, the computing device may account for the displacement distance by adjustment of the relative position of the powder stream to the melt pool. The computing device may similarly account for displacement distances resulting from the force of gravity or other forces, such as those forces due to powder carrier gases rebounding from the component or the like.

[0031] The displacement distance may depend on a number of additional parameters of the additive manufacturing system. For example, a deposition head speed, size distribution and density of the powder, energy beam shape, energy beam power and spot size, melt pool size, powder feed rate, a process gas flow rate, or velocity, or direction, and/or working distance may all be settings to the system which impact the optimized relative position of the powder stream to the melt pool. In some examples, the computing device may receive indications of some or all of these additional parameters, and may adjust the relative position of the powder stream to the melt pool based at least partially on one or more of these parameters. For example, these and/or other parameters may be input into the machine learning algorithm, which may output a control signal to position the energy delivery device, the powder delivery device, or both during an additive manufacturing technique. While primarily described herein as systems and techniques configured to align the powder stream with the melt pool, in some examples the disclosed systems and techniques may deliberately misalign and maintain and control the misalignment of the powder stream to the melt pool where such misalignment is found advantageous for a specific process.

[0032] In some examples, the computing device may maintain the relative position of the powder stream to the melt pool throughout a portion of the additive manufacturing process. For example, the relative position may be maintained throughout deposition of a layer. Controlled maintenance

of the relative position of the powder stream to the melt pool may yield improved quality and uniformity of the part.

[0033] FIG. 1 is a conceptual block diagram illustrating aspects of an example additive manufacturing system 10. Additive manufacturing system 10 includes several components configured to monitor mass flow, and several components configured to monitor energy (e.g., heat flux) within system 10. System 10 includes a powder source mass sensor 44, a powder flow monitoring system (PFMS) 18, and a topology sensor 48. These components are configured to monitor mass flow of powder within additive manufacturing system 10 during an additive manufacturing technique. In the example illustrated in FIG. 1, additive manufacturing system 10 further includes a computing device 12, a powder delivery device 14, an energy delivery device 16, a stage 20, a powder source 42, powder source mass sensor 44, and topology sensor 48. Computing device 12 is operably connected to powder delivery device 14, energy delivery device 16, PFMS 18, stage 20, powder source 42, powder source mass sensor 44, and topology sensor 48. FIG. 1 thus illustrates mass flow monitoring and other aspects of example additive manufacturing system 10. To simplify illustration of FIG. 1 and improve clarity of the figure, further aspects of additive manufacturing system 10 are shown in FIG. 5 and described below with reference to FIG. 5, which is more directed toward heat flow aspects of system 10.

[0034] Stage 20 is configured to mechanically support a component 22 during an additive manufacturing technique. Component 22 may be considered in-situ when mechanically supported by stage 20. In some examples, stage 20 is movable relative to energy delivery device 16 and/or energy delivery device 16 is movable relative to stage 20. Similarly, stage 20 may be movable relative to powder delivery device 14 and/or powder delivery device 14 may be movable relative to stage 20. For example, stage 20 may be translatable and/or rotatable along at least one axis to position component 22 relative to energy delivery device 16 and/or powder delivery device 14. Similarly, energy delivery device 16 and/or powder delivery device 14 may be translatable and/or rotatable along at least one axis to position energy delivery device 16 and/or powder delivery device 14, respectively, relative to component 22. Stage 20 may be configured to selectively position and restrain component 22 in place relative to stage 20 during manufacturing of component 22.

[0035] Powder source 42 is the source of powder for powder stream 30. Powder source 42 may include any suitable container or enclosure, such as a hopper, configured to hold powder. Powder source 42 also may include mechanism for entraining the powder in a gas flow. For instance, powder source 42 may be coupled to a gas source, which provides a gas flowing through powder source 42 and entraining powder within the gas flow. Additionally, or alternatively, powder source 42 may include an agitator configured to agitate the powder and increase entrainment of the powder in the gas stream.

[0036] System 10 may include a powder source mass sensor 44 associated with powder source 42. Powder source mass sensor 44 may be configured to quantify loss of mass in the powder source 42 or, alternatively, a mass flow out of powder source 42.

[0037] Powder source 42 is fluidically coupled to powder delivery device 14 via a flow path 46. Flow path 46 may include any suitable structure(s) defining an enclosed flow between powder source 42 and powder delivery device, including conduit, pipe, tubes, or the like. Although not shown in FIG. 1, for at least part of flow path 46 between powder source 42 and nozzles of powder delivery device 14, flow path 46 may split into multiple, parallel sections, e.g., one for each nozzle. Further, although not shown in FIG. 1, in some examples, flow path 46 may include one or more nozzles for controlling flow through flow path 46 as a whole or portions of flow path 46 (e.g., a section associated with a particular nozzle of powder delivery device 14).

[0038] Powder delivery device 14 may be configured to deliver powder to selected locations of component 22 being formed via a powder stream 30. Powder delivery device 14 may include one or more nozzles that each output powder. The combined powder defines powder stream 30. In

some examples, powder delivery device **14** includes a single nozzle, which may be point nozzle, or a single nozzle that is an annular channel. In other examples, powder delivery device **14** includes a plurality of nozzles (e.g., three nozzles or four nozzles). Regardless of the number of nozzles, powder delivery device **14** may output a powder stream that is focused at a focus plane. In some examples, the powder delivery device may define a powder stream central axis. The powder stream central axis may be coincident with a delivery channel in examples where the powder delivery device includes a single nozzle. In examples where the powder delivery device includes multiple nozzles, the powder stream central axis may be defined at the downstream end of the powder delivery device as normal to build surface **28** and equidistant from each delivery nozzle of the plurality of delivery nozzles. As powder delivery device **14** is movable in the z-axis shown in FIG. **1** relative to component **22**, the focal plane of powder delivery device **14** also may be movable in the z-axis relative to component **22**, such that the focus plane may be controlled to be substantially coincident with build surface **28**.

[0039] At least some of the powder in powder stream **30** may impact a melt pool **32** in component **22**. At least some of the powder that impacts melt pool **32** may be joined to component **22**. In some examples, powder delivery device **14** may be mechanically coupled or attached to primary energy delivery device **16** to facilitate delivery of powder stream **30** and energy **34** for forming melt pool **32** to substantially the same location adjacent to component **22**. As will be further described below, the relative position of powder stream **30** to melt pool **32** may be adjustable by computing device **12**, which may be advantageous when compared to conventional additive manufacturing systems where the spatial relationship between powder stream **30** and melt pool **32** is fixed.

[0040] Energy delivery device **16** may include an energy source, such as a laser source, an electron beam source, plasma source, or another source of energy that may be absorbed by component **22** to form a melt pool **32** and/or be absorbed by powder in powder stream **30** to be added to component **22**. Example laser sources include a CO laser, a CO.sub.2 laser, a Nd:YAG laser, or the like. In some examples, the energy source may be selected to provide energy with a predetermined wavelength or wavelength spectrum that may be absorbed by component **22** and/or the powder to be added to component **22** during the additive manufacturing technique.

[0041] In some examples, energy delivery device **16** also includes an energy delivery head, which is operatively connected to the energy source. The energy delivery head may aim, focus, or direct energy **34** toward predetermined positions at or adjacent to a surface of component **22** during the additive manufacturing technique. As described above, in some examples, the energy delivery head may be movable in at least one dimension (e.g., translatable and/or rotatable) under control of computing device **12** to direct energy **34** toward a selected location at or adjacent to build surface **28** of component **22**. Energy delivery device **16** may be configured to focus energy **34** from the energy source on a local spot on build surface **28** to generate melt pool **32**. As will be further described below, energy delivery device **16** may include one or more mechanisms to adjust the position of energy **34** and thus melt pool **32**. For example, energy delivery device **16** may direct energy **34** through an optical system that includes one or more galvanometers and/or one or more lenses. Additionally, or alternatively, energy delivery device **16** may be mounted on one or more adjustable support members, which may be adjusted by computing device **12**. The galvanometers, lenses, and/or adjustable support members may be adjusted by computing device **12** to modify and selectively tailor the position of energy **34**, and, accordingly, the position of melt pool **32** on build surface **28**.

[0042] In some examples, at least a portion of primary energy delivery device **16** and powder delivery device **14** may be combined or attached to each other. For example, a deposition head (e.g., deposition head **54** of FIG. **2**) may include part of powder delivery device **14** (e.g., internal channels and powder nozzle(s) **56** for forming powder stream **30** and directing powder stream **30** toward build surface **28**) and part of primary energy delivery device **16** (e.g., the energy delivery head). As shown in FIG. **1**, in some examples, primary energy delivery device **16** may be arranged

of configured such that energy **34** and powder stream **30** both exit from a common deposition head (**54**, FIG. 2) and are directed toward build surface **28**. For instance, energy **34** may pass through a central channel (e.g., formed along central longitudinal axis L, FIG. 2) within the deposition head and exit a central aperture in the deposition head, while fluidized powder may flow through internal channels and powder nozzle(s) **56** for forming powder stream **30** and directing powder stream **30** toward build surface **28**. Such an arrangement between primary energy source **16** and powder delivery device **14** may be called an “on-axis” arrangement of primary energy source **16**, because both energy and powder may be delivered coaxially with a central longitudinal (Z-direction) axis of the deposition head.

[0043] System **10** also includes powder flow monitoring system (PFMS) **18**. PFMS **18** is configured to image at least a portion of powder stream **30** to detect powder flowing between powder delivery device **14** and build surface **28**. For example, PFMS **18** may include an illumination device and an imaging device. In some examples, the illumination device may include one or more light sources. For instance, the illumination device may include one or more structured light devices, such as one or more lasers. The illumination device is configured to illuminate a plane of powder stream **30** at image plane **38**, e.g., a plane substantially perpendicular to an axis extending between powder delivery device **14** and build surface **28** (e.g., central longitudinal axis L).

[0044] The imaging device of PFMS **18** is configured to image at least some of the illuminated powder. The imaging device may have a relatively high data acquisition speed (e.g., frame rate), such greater than 1000 Hz. Because of the velocity of the powder in powder stream **30**, even such a frame rate may image only a fraction of the powder flowing between powder delivery device **14** and build surface **28**. In some examples, the imaging device may be a camera.

[0045] In some examples, PFMS **18** also includes a housing configured to enclose the illumination device and the imaging device. The housing may be configured to protect the illumination device and the imaging device from damage due to the harsh conditions to which PFMS **18** may be exposed during use. For example, the housing may protect the illumination device and the imaging device from powder deflections from powder stream **30** off build surface **28**, may cool the illumination device and the imaging device to remove heat incident on PFMS **18** from melt pool **32** and energy delivery device **16**, or the like.

[0046] PFMS **18** may be positionally fixed relative to powder delivery device **14** and/or energy delivery device **16**, e.g., in the x-y plane shown in FIG. 1. This may help maintain a relative x-y position of PFMS **18** and the image plane of the imaging device relative to powder stream **30**. This may facilitate analysis of image data captured by the imaging device.

[0047] PFMS **18** may be movable in the z-axis direction of FIG. 1 (e.g., parallel to a longitudinal axis extending from powder delivery device **14** to build surface **28**). This may enable movement of image plane **38** along the z-axis of FIG. 1 (e.g., parallel to a longitudinal axis extending from powder delivery device **14** to build surface **28**). This may allow PFMS **18** to image powder stream **30** at different positions between powder delivery device **14** and build surface **28**. In this way, PFMS **18** may analyze powder stream **30** along powder stream **30** to help determine parameters of powder stream **30** along its length.

[0048] In some example, PFMS **18** may be positionally fixed relative to powder delivery device **14** and/or energy delivery device **16** and movable parallel to a longitudinal axis extending from powder delivery device **14** to build surface **28** by an adjustable z-stage **40**. Adjustable z-stage **40** may be attached to energy delivery device **16**, powder delivery device **14**, or a portion of system **10** that moves energy delivery device **16** and/or powder delivery device **14**, such that PFMS **18** moves in the x-y axis in registration with energy delivery device **16** and/or powder delivery device **14**.

[0049] Adjustable z-stage **40** may be controlled by computing device **12** to position PFMS **18** and image plane **38** relative to powder stream **30**. Further, computing device **12** may control adjustable z-stage **40** to move PFMS **18** vertically and out of the way to allow powder delivery device **16** and

energy delivery device **16** access to physically constrained areas, e.g., between vanes of a doublet or triplet of a nozzle guide vane for a gas turbine engine.

[0050] System **10** further includes a topology sensor **48**. Topology sensor **48** is configured to monitor an amount of powder captured by melt pool **32** by imaging melt pool **32** and the added material, allowing the mass to be quantified (e.g., by computing device **12**) using the dimensions of the added material and density of the material (powder). In some examples, topology sensor **48** includes a laser and a sensor (e.g., an imaging device, such as a camera), which senses laser light reflected by the structure being imaged (e.g., melt pool **32** and the added material). The laser may have a defined wavelength, which may affect the resolution of the topology sensor **48**. In some examples, the wavelength and sensor may be selected such that the resolution of topology sensor **48** is as great as about 10 microns (e.g., about 6 microns).

[0051] In some examples, topology sensor **48** may be positioned substantially directly above component **22** (e.g., along a central axis of powder delivery device **14**, energy delivery device **16**, or a common deposition head that includes both powder delivery device **14** and energy delivery device **16**) and may include an interferometer, which provides depth information based on the time from outputting a laser pulse to the sensing of the reflected light. In other examples, topology sensor **48** may be positioned at an offset with respect to component **22** such that the sensor senses depth information without using an interferometer.

[0052] In some examples, topology sensor **48** may be integral with system **10**, e.g., disposed within the enclosure or working area of system **10**. In other examples, topology sensor **48** may be an add-on component to system **10**. For example, the enclosure in which the additive manufacturing technique is performed may include a transparent window, and topology sensor **48** may be positioned outside of the enclosure and may image component **22** through the transparent window.

[0053] Although a topology sensor **48** is described in the examples of this disclosure, in other examples, another metrology device may be utilized to determine the amount of powder captured by melt pool **32**. For example, another type of light source may be used. In some examples, if another type of light source is used, component **22** or stage **20** may include one or more features that serve as indicators of scale. Furthermore, although described as a single topology sensor **48**, more than one sensor may be used, and may employ more than one of the technologies described above.

[0054] Computing device **12** may control components of system **10** and may include, for example, a desktop computer, a laptop computer, a workstation, a server, a mainframe, a cloud computing system, or the like. Computing device **12** may control operation of system **10**, including, for example, powder delivery device **14**, energy delivery device **16**, PFMS **18**, stage **20**, powder source **42**, powder source mass sensor **44**, and/or topology sensor **48**. Computing device **12** may be communicatively coupled to powder delivery device **14**, energy delivery device **16**, PFMS **18**, stage **20**, powder source **42**, powder source mass sensor **44**, and/or topology sensor **48** using respective communication connections. In some examples, the communication connections may include network links, such as Ethernet, ATM, or other network connections. Such connections may be wireless and/or wired connections. In other examples, the communication connections may include other types of device connections, such as USB, IEEE 1394, or the like.

[0055] Computing device **12** may include one or more processors. Example of processors include, but are not limited to, one or more microprocessors, digital signal processors (DSPs), application specific integrated circuits (ASICs), field programmable gate arrays (FPGAs), or any other equivalent integrated or discrete logic circuitry, as well as any combinations of such components. Computing device **12** may include a memory, and the memory may store instructions for various operations of system **10**.

[0056] Although FIG. **1** illustrates a single computing device **12** and attributes all control and processing functions to that single computing device **12**, in other examples, system **10** may include multiple computing devices **12**, e.g., a plurality of computing devices **12**. In general, control and

processing functions described herein may be divided among one or more computing devices. For instance, system **10** may include a controller for energy delivery device **16**, powder delivery device **14**, and stage **20**, a separate controller for PFMS **18**, and a separate computing device for analyzing data obtained by PFMS **18**, mass sensor **44**, and topology sensor **48**. As another example, system may include a dedicated controller for each of energy delivery device **16**, powder delivery device **14**, stage **20**, PFMS **18**, and topology sensor **48**, and a separate computing device for coordinating control of powder delivery device **14**, energy delivery device **16**, PFMS **18**, stage **20**, powder source **42**, powder source mass sensor **44**, and/or topology sensor **48** and analyzing data obtained by PFMS **18**, powder source mass sensor **44**, and/or topology sensor **48**. Other examples of computing system architectures for controlling system **10** and analyzing data obtained from system **10** will be apparent and are within the scope of this disclosure.

[0057] Computing device **12** may control operation of powder delivery device **14**, primary energy delivery device **16**, secondary energy delivery device **17**, adjustable z-stage **40**, stage **20**, and/or topology sensor **48** to position component **22** relative to powder delivery device **14**, energy delivery device **16**, PFMS **18**, and topology sensor **48**. For example, as described above, computing device **12** may control stage **20** and powder delivery device **14**, energy delivery device **16**, adjustable z-stage **40**, and/or topology sensor **48**, to translate and/or rotate along at least one axis to position component **22** relative to powder delivery device **14**, energy delivery device **16**, PFMS **18**, and topology sensor **48**. Positioning component **22** relative to powder delivery device **14**, energy delivery device **16**, PFMS **18**, and topology sensor **48** may include positioning a predetermined surface (e.g., build surface **28**, a surface to which material is to be added) of component **22** in a predetermined orientation relative to powder delivery device **14**, energy delivery device **16**, PFMS **18**, and/or topology sensor **48**.

[0058] Computing device **12** may control system **10** to deposit layers **24** and **26** to form component body **25** and eventually finished component **22**. As shown in FIG. **1**, component **22** may include a first layer **24** and a second layer **26**, although many components may be formed of additional layers, such as tens of layers, hundreds of layers, thousands of layers, or the like. Component **22** in FIG. **1** is simplified in geometry and the number of layers compared to many components formed using additive manufacturing techniques. Although techniques are described herein with respect to component **22** including first layer **24** and second layer **26**, the technique may be extended to components **22** with more complex geometry and any number of layers. Furthermore, although component **22** is illustrated as being uniform, in some examples component **22** may be functionally-graded and include at least two different portions having different selectively tailored properties.

[0059] To form component **22**, computing device **12** may control powder delivery device **14** and energy delivery device **16** to form, on build surface **28** of first layer **24** of material, a second layer **26** of material using an additive manufacturing technique. Computing device **12** may control primary energy delivery device **16** to deliver energy **34** to a volume at or near surface **28** to form melt pool **32**. For example, computing device **12** may control the relative position of energy delivery device **16** and stage **20** to direct energy to the volume. Computing device **12** also may control powder delivery device **14** to deliver powder stream **30** to melt pool **32**. For example, computing device **12** may control the relative position of powder delivery device **14** and stage **20** to direct powder stream **30** at or on to melt pool **32**. The position of powder stream **30** and melt pool **32** may be independently controlled by computing device **12**, such that the relative position of powder stream **30** to melt pool **32** may be selectively controlled as part of an additive manufacturing technique, in accordance with examples of this disclosure. The relative position of powder stream **30** to melt pool **32** may even be independently controlled when powder delivery device **14** and energy delivery device **16** are parts of a common deposition head (**54**, FIG. **2**). Such independent control of powder delivery device **14** and energy delivery device **16** during an additive manufacturing process may permit adjustment of the relative position of powder stream **30** to melt

pool 32 to account for settings and parameters of system 10 during operation.

[0060] Computing device 12 may then control a z-axis position of stage 20 and/or powder delivery device 14 and energy delivery device 16 such that melt pool 32 will be formed on surface 36 of second layer 26, and may control powder delivery device 14 and energy delivery device 16 to move energy 34 and powder stream 30 along build surface 28 in a pattern until layer 26 is complete. Computing device 12 may control powder delivery device 14 and energy delivery device 16 similarly until all layers are formed to define a completed component 22.

[0061] Computing device 12 may control powder delivery device 14 and primary energy delivery device 16 to move energy 34 and powder stream 30 along build surface 28 in a pattern until layer 26 is complete. As mentioned above, powder delivery device 14 and energy delivery device 16 may be parts of a common deposition head, and computing device 12 may control the deposition head (54, FIG. 2) to move along a toolpath to deposit layer 26. Computing device 12 may receive, from PFMS 18, data indicative of the position of powder stream 30. Computing device 12 may also receive, from an optical system configured to observe the melt pool, data indicative of a position of the melt pool on build surface 28. The absolute position of powder stream 30 and melt pool 32 may be defined relative to common deposition head (54, FIG. 2), or may be defined with respect to a point cloud model of dimensions of final component 22. Computing device 12 may determine the relative position of powder stream 30 to melt pool 32 based on the determined absolute positions of powder stream 30 and melt pool 32. Computing device 12 may control powder delivery device 14 and/or energy delivery device 16 based on the determined relative position of powder stream 30 to melt pool 32.

[0062] In some examples, computing device 12 may store/execute one or more machine learning models which may be used to adapt control of powder delivery device 14, primary energy delivery device 16, secondary energy delivery device 17, or another component. For example, data captured by one or more thermal sensors, energy delivery device 16, PFMS 18, topology sensor 48, mass source 44, or other components of system 10 may be used to train the machine learning device. Furthermore, additional parameters of system 10 may be inputs to a machine learning model, such as operational settings of system 10.

[0063] FIG. 2 is a conceptual and schematic diagram illustrating example additive manufacturing system 100. Additive manufacturing system 100 of FIG. 2 may be an example of additive manufacturing system 10 of FIG. 1. System 100 includes an example powder flow monitoring system 50 configured to monitor powder flow between a powder delivery device 52 and a build surface (not shown in FIG. 2) during an additive manufacturing technique. Powder delivery device 52 may be an example of powder delivery device 14 of FIG. 1, and PFMS 50 may be an example of PFMS 18 of FIG. 1.

[0064] Powder delivery device 52 includes a deposition head 54 that carries a plurality of delivery nozzles 56. Plurality of delivery nozzles 56 output a powder stream 58 toward the build surface. As shown in FIG. 2, the powder stream 58 may be focused at a focal plane, such that powder stream 58 is converging toward the focal plane and diverging away from the focal plane. As discussed above, deposition head 54 may further include energy delivery device 16, which is not illustrated in FIG. 2 for improved clarity. Powder delivery device 52 may define powder stream central axis L. In examples where powder delivery device 52 includes a single delivery nozzle 56, central axis L may pass through the single delivery nozzle. In some examples, as illustrated, powder delivery device 52 may include plurality of delivery nozzles 56, and powder stream central axis L may be defined between point P1 and point P2. Point P1 may be the point equidistant from plurality of delivery nozzles 56 on the downstream end, relative to powder flowing through powder delivery device 52, of powder delivery device 52. Point P2 may be the point at which powder from the plurality of delivery nozzles 56 converges, which may be at the build surface (28, FIG. 1) of a component. In some examples, the energy delivery device (not illustrated in FIG. 2 for clarity), may be configured to deliver energy to the build surface parallel to (e.g., coincident with) powder

stream central axis L.

[0065] PFMS **18** includes a housing **60** (also referred to as an enclosure), which encloses an imaging device **62** and an illumination device **64**. In some examples, imaging device **62** may be a high-speed camera and illumination device **64** may be laser illuminator. Housing **60** is attached to an adjustable z-stage **66** by a bracket **68**.

[0066] Housing **60** may enclose imaging device **62** and illumination device **64** and help protect imaging device **62** and illumination device **64** from a surrounding environment. For instance, housing **60** may surround imaging device **62** and illumination device **64** and prevent any powder that reflects from the build surface toward PFMS **18** from impacting imaging device **62** or illumination device **64**.

[0067] Further, housing **60** may be configured to cool imaging device **62** and illumination device **64**. Imaging device **62** and illumination device **64** may be exposed to heat from the melt pool at the build surface and energy from the energy delivery device. Imaging device **62** and illumination device **64** may be relatively sensitive to heat and have improved operational lifetime if maintained and operated below a certain temperature. PFMS **50** may include a cooling system **70** that removes heat from within housing **60** to cooling imaging device **62** and illumination device **64**. For instance, cooling system **70** may include cooling fluid circuit through which a cooling fluid flows, and housing **60** may include part of the cooling circuit. In some examples, housing **60** may be formed from a material having relatively high thermal conductivity, such as aluminum, to help transfer heat from within housing **60** to cooling system **70** (e.g., a cooling fluid flowing through cooling system **70**).

[0068] As described above, PFMS **50** may be configured to measure powder flow of powder stream **58** (FIG. 2) at one or more axial (or longitudinal) locations of powder stream **58** and determine one or more parameters associated with the powder flow. For instance, PFMS **50** may be determine a position of powder stream, either absolutely with respect to system **100** or with respect to deposition head **54**, the position of which may be known relative to system **100**. For instance, illumination device **64** may illuminate powder of powder stream **58** in a plane oriented substantially orthogonal to a longitudinal axis that extends from powder delivery device **52** to the build surface. PFMS **50** may be positioned at a selected axial or longitudinal location to image a selected axial or longitudinal position between powder delivery device **52** and the build surface. Imaging device **62** may be a camera configured to image at least some of the illuminated powder.

[0069] FIG. 3 is a conceptual diagram illustrating an example of portions of a powder stream imaged by a powder flow monitoring system. As shown in FIG. 3, since powder is flowing in powder stream **358** at a relatively high velocity, imaging device **362** may not capture images of all the powder in powder stream **358**. The fraction of powder that imaging device **362** captures images of may be a function of average powder velocity at the image plane and a frame rate or capture speed of imaging device **362**. This is represented in FIG. 3 as “sampled” particles and “missed population” particles. The fraction of particles imaged by imaging device **362** may, in some examples, be less than about 50%, less than about 40%, less than about 30%, less than about 25%, less than about 20%, or less than about 15%.

[0070] PFMS **50** may include a computing device (e.g., computing device **12** of FIG. 1) configured to analyze images captured by imaging device **62** to identify a number of particle detections in each captured image and, optionally, derive further parameters from the number of particle detections. As such, computing device **12** may receive image data representing an image captured by imaging device **362**. The image data may include representations of illuminated powder of powder stream **358**, as imaged by imaging device **362** (e.g., as captured in an image frame by imaging device **362**). Computing device **12** may generate a representation of powder stream based on the image data and output the representation of the powder stream for display at a display device.

[0071] Computing device **12** may analyze the image data representative of powder stream **358** to determine one or more aspects of the position of powder stream **358**. For instance, computing

device **12** may recognize powder particles **302**, **304**. Powder particles **302**, **304** may be located at respective extremes of the width of powder stream **358**. In some examples, for example where the powder delivery device includes on a single delivery nozzle, powder stream central axis **L** may be defined as midway between powder particles **302**, **304**. Computing device **12** may determine the position of powder stream **358** based on the position of particles **302**, **304**, powder stream central axis **L**, or combinations thereof.

[0072] In some examples, computing device **12** may determine a powder mass flow represented by the image data. To do so, computing device **12** may identify a number of powder particles within each image frame. In some examples, computing device **12** additionally may identify a size and/or shape of each powder particle within each image frame. Computing device **12** may implement any suitable image analysis technique to identify powder particles, and, optionally, size and/or shape of powder particles. Since the position of imaging device **362**, either absolutely within the additive manufacturing system or relatively with respect to an associated deposition head, may be known, the position of powder stream **358** may be determined by the position of powder stream **358** within the image frame.

[0073] Once computing device **12** has identified a number of powder particles within an image frame, computing device **12** may determine a mass flow based on the number of powder particles. For example, computing device **12** may determine the mass flow based on a calibration equation or calibration curve. FIG. **5** is an example calibration curve of particle detections versus mass flow. As shown in FIG. **4**, the relationship between particle detections may be substantially linear.

[0074] The relationship between particle detections and mass flow may be determined experimentally. For instance, the relationship between particle detections and mass flow may be determined for each powder type (e.g., composition, size distribution, or both), as each powder type may have a different relationship between particle detections and mass flow. The relationship may be determined experimentally by flowing a known mass of powder at a known rate, and imaging the powder. By doing this multiple times at multiple rates, the calibration curve may be generated. The curve, in the form of an equation, a look-up table, or the like, may be stored in computing device **12**, and computing device **12** may use the calibration curve to determine mass flow of a similar type of powder at a different flow rate based on particle detections.

[0075] In some examples, computing device **12** may receive image data representative of a sequence of images of illuminated powder in powder stream **58**. Each image may be associated with a time. As such, computing device **12** may select one or more images of the sequence of images and analyze the one or more images. For each selected image, computing device **12** may identify a number of particle detections and, optionally, determine a mass flow associated with powder stream **58** for each image frame.

[0076] As described above, system **10** may include both mass flow monitoring and heat flow monitoring. FIG. **1** best illustrates the mass flow monitoring aspects of system **10**. FIG. **5** is a conceptual block diagram illustrating further aspects of system **10**, best illustrating the heat flow monitoring aspects of the example system. System **10** includes an optical system **80** for observing thermal emissions around melt pool **32**, a melt pool monitor (MP monitor) **15** including a thermal camera for monitoring a size and/or temperature of melt pool **32**, and an optional off-axis camera **21**. Identical reference numerals in FIGS. **1** and **5** refer to the same parts. Further, those common parts are the same or substantially identical, aside from any differences described herein. As shown in FIG. **5**, energy delivery device **16** includes an optical system **80**.

[0077] During additive manufacturing, component **22** is built up by adding material to component **22** in sequential layers. The final component is composed of a plurality of layers of material. Energy delivery device **16** may direct energy **34** at build surface **28** of first layer **24** to form melt pool **32**. Powder delivery device **14** may deliver powder stream **30** to melt pool **32**, where at least some of the powder at least partially melts and is joined to first layer **24**. Melt pool **32** cools as energy **34** is no longer delivered to that location of first layer **24** (e.g., due to energy delivery device

16 scanning energy 34 over the surface of first layer 24). The temperature and cooling rate of melt pool 32 and the surrounding areas of first layer 24 affect the microstructure, porosity, temper, and other properties of component 22 formed using the additive manufacturing technique. Further, these and other properties of component 22 may be impacted by the relative position of powder stream 30 to melt pool 32. Optical system 80, MP monitor 15, and/or camera 21 may capture data indicative of the position of melt pool 32, and computing device 12 may analyze the captured data and determine the position of melt pool 32, either absolutely within system 10 or relatively with respect to an associated deposition head.

[0078] Optical system 80 may include an imaging device and an associated optical train, which senses emissions at or near component 22 during the additive manufacturing technique. For example, optical system 80 may include a visible light imaging device, an infrared imaging device, or an imaging device that is configured (e.g., using a filter) to image a specific wavelength or wavelength range.

[0079] The optical train may include one or more reflective, refractive, diffractive optical components configured to direct light to the imaging device. For example, the optical train may be configured to direct light from near component 22 and/or melt pool 32 to the imaging device. In some examples, at least a portion of the optical train is coaxial with the axis at which energy delivery device 16 outputs energy, and the at least a portion of the optical train may be attached to or otherwise configured to move with the portion of energy delivery device 16 that directs or focuses energy 34 at or near the surface of component 22. In this way, optical system 80 may move with energy delivery device 16 and track melt pool 32 as melt pool 32 moves across component 22, without needing to correct for any offsets between energy delivery device 16 and optical system 80 and/or needing to correct for geometry of component 22. In other examples, the optical train may not be coaxial with the axis at which energy delivery device 16 outputs energy 34, and computing device 12 may be configured to compensate for the offset and any affects this may have on the imaging, including shadowing, interference, geometry of component 22, or the like. Off-axis camera 21, which is a second camera not coaxial with the axis at which energy delivery device 16 outputs energy 34, may be configured to determine the position of melt pool 32 within system 10 by imaging energy 34 and/or melt pool 32 from a known (e.g., fixed) position within system 10.

[0080] In some examples, optical system 80 may include an occulting device. The occulting device is configured to reduce or block emissions (e.g., thermal emissions) that originate from the energy output by energy delivery device 16 and/or near a center of melt pool 32, which otherwise obfuscate emissions from solidifying regions of material at or near the edge of melt pool 32 and outside of melt pool 32. The occulting device may be a rigid occulting device or a dynamic occulting device. A rigid occulting device reduces or blocks emissions from a fixed region, e.g., from the energy 34 output by energy delivery device 16. For instance, a rigid occulting device may include a device with fixed dimensions that is opaque to wavelengths of interest. As another example, a rigid occulting device may include an apodizing lens in which a center of the lens is substantially opaque to wavelengths of interest and opacity decreases as a function of radius.

[0081] A dynamic occulting device is configured to be controlled to occult different regions, e.g., different sizes and/or shapes. A dynamic occulting device may include a rigid occulting device that is mounted to a device that can translate the rigid occulting device along and/or perpendicularly to the optical axis. As another example, a dynamic occulting device may include an opaque and viscous liquid, such as mercury, contained between two substrates. The substrates are substantially transparent to the wavelength(s) of interest. One or both of the substrates may be movable relative to the other substrate to control the distance between the substrates. By reducing the distance between the substrates, the size of the occulting region may increase. By increasing the distance between the substrates, the size of the occulting region may decrease. As a third example, a dynamic occulting device may include a digital micromirror device. Computing device 12 may control the micromirrors of the digital micromirror device to direct emissions that originate from

energy **34** output by energy delivery device **16** and/or near a center of the melt pool away from the imaging device. A digital micromirror device may enable control of both the size and shape of the region of emissions that are occulted. As will be further discussed below, computing device **12** may a digital micromirror device within energy delivery device **16**, which may be a galvanometer, or another digital micromirror device, to adjust the position of energy **34**, and this the position of melt pool **32**.

[0082] FIG. **6** is a conceptual block diagram illustrating an example optical system **80** for observing thermal emissions at and/or around a melt pool **32** and or a focused spot on a build surface **28** where a melt pool is not formed (e.g., by second energy delivery device **17**, FIGS. **1** and **5**) formed during an additive manufacturing technique. Optical system **80** includes an optical train that includes first imaging optics **92**, occulting device **94**, second imaging optics **96**, and imaging device **98**. Imaging device **98** may be any suitable imaging device, including, for example, a visible light imaging device, an infrared imaging device, an imaging device that is configured (e.g., using a filter) to image a specific wavelength or wavelength range, a two color pyrometry imaging device, or the like.

[0083] First and second imaging optics **92** and **96** may each include one or more optical devices used to direct light to imaging device **98**. For example, First and second imaging optics **92** and **96** may each include one or more refractive optical device (e.g., a lens), one or more reflective optical device (e.g., a mirror), one or more diffractive optical devices (e.g., a grating), one or more dichroic optical devices (e.g., a dichroic filter or mirror), or the like. Although two sets of imaging optics **92** and **98** are shown in FIG. **6**, in other examples, system **80** may include a single set of imaging optics or more than two sets of imaging optics.

[0084] Occulting device **94** is positioned within the optical train between first imaging optics **92** and second imaging optics **96**. In other example, occulting device **94** may be positioned between imaging device **98** and imaging optics **96** or after before imaging optics **92**. In some examples, occulting device **94** is positioned as the optical component nearest imaging device. This effectively results in removal of the portion of the image which occulting device **94** blocks. In other examples, occulting device **94** is positioned at another position within the optical train **80** where the image of component **22** resolves. Imaging optics **96** then may be configured to image occulting device **94** onto imaging device **98**.

[0085] As shown in FIG. **6**, in some examples, at least a portion of optical system **80** is coaxial with the axis at which energy delivery device **16** outputs energy **34**. For example, at least a portion of second imaging optics **92** (e.g., the portion at which thermal emissions **104** is incident upon second imaging optics **92**) may be coaxial with the axis at which energy delivery device **16** outputs energy **34**. This may reduce image manipulation that otherwise may be applied to the resulting image to correct for geometry of component **22**, angular offset of optical system **80** relative to energy delivery device **16**, shadowing due to the angular offset, interference, or the like. In other examples, optical system **80** (e.g., the portion at which thermal emissions **104** are incident upon second imaging optics **92**) may not be coaxial with the axis at which energy delivery device **16** outputs energy **34**, and computing device **12** (FIG. **1**) or another computing device may manipulate the resulting image to compensate for geometry of component **22**, angular offset of optical system **80** relative to energy delivery device **16**, shadowing due to the angular offset, interference, or the like.

[0086] FIG. **6** also illustrates energy delivery device **16** outputting energy **34**, which is incident upon component **22** and results in formation of melt pool **32**. Surrounding melt pool is a cooling zone **102**, in which temperature gradients from the temperature of melt pool **32** to ambient temperature are present. As shown in FIG. **6**, melt pool **32** and cooling zone **102** emit thermal emissions **104** (e.g., thermal radiation), which travel through optical system **80** to imaging device **98**, which images the thermal emissions **104**. Occulting device **94** occults (e.g., reduces the intensity of or substantially eliminates) thermal emissions **104** from a selected region, e.g., a region

corresponding to energy **34** and at least a portion of melt pool **32**. This may allow imaging device **98** to more effectively image relatively lower intensity thermal emissions from at or near the edge of melt pool **32** and within cooling zone **102**. This may enable more accurate measurement of temperatures within the cooling zone **102**, and heat flow within cooling zone **102**.

[0087] Returning to FIG. 5, system **10** also includes melt pool monitor (“MP monitor”) **15**. Melt pool monitor **15** may include a sensor for monitoring a characteristic of melt pool **32**. The monitored characteristic may be indicative of a temperature of melt pool **32**. For example, the sensor may include an imaging system, such as a visual or thermal camera, e.g., camera to visible light or infrared (IR) radiation. A visible light camera may monitor the geometry of the melt pool, e.g., a width, diameter, shape, or the like. A thermal (or IR) camera may be used to detect the size, temperature, or both of the melt pool. In some examples, a thermal camera may be used to detect the temperature of the melt pool at multiple positions within the melt pool, such as a leading edge, a center, and a trailing edge of the melt pool. In some examples, the imaging system may include a relatively high-speed camera capable of capturing image data at a rate of tens or hundreds of frames per second or more, which may facilitate real-time detection of the characteristic of the melt pool. In some examples, MP monitor **15** may capture data at a sequence of particular points in time including a first point in time, a second point in time, etc. In some examples, data from melt pool monitor **15** may be analyzed by computing device **12** to determine a position of melt pool **32** on build surface **28**. For example, computing device **12** may determine a center point of melt pool **32**. [0088] FIG. 7 is a process flow diagram illustrating an additive manufacturing monitor and control technique. The technique of FIG. 7 may be implemented by system **10** of FIGS. 1 and 5 and will be described with concurrent reference to FIGS. 1 and 5. However, it will be appreciated that system **10** may perform other techniques and the technique of FIG. 7 may be performed by other systems. For example, system **100** of FIG. 2 may perform the described technique.

[0089] One or more computing devices **12** may be configured to control a powder feed rate output by powder source **42** (see top left of FIG. 7). For instance, one or more computing devices **12** may be configured to control an agitator of powder source **42**, a gas flow rate of gas flowing through powder source **42**, a position of one or more valves within flow path **46**, or the like to control a powder feed rate output by powder source **42**.

[0090] One or more computing devices **12** may be configured to receive data from one or more mass flow monitoring sensors, including PFMS **18**, powder flow mass sensor **44**, and/or topology sensor **48**. Data received from powder flow mass sensor **44** indicates a mass flow of powder from powder source **42** to powder delivery device. Data from PFMS **18** indicates a mass flow of powder in powder stream **30** between powder delivery device **14** to adjacent melt pool **32**. Data from topology sensor **48** indicates powder mass captured by melt pool **32** and added to component **22**.

[0091] One or more computing devices **12** may calculate one or more mass flow-related metrics based on the data received from PFMS **18**, powder flow mass sensor **44**, and/or topology sensor **48**. For example, one or more computing devices **12** may determine a capture efficiency by determining a fraction or percentage of powder from powder stream **30** that is captured by melt pool **32** and added to component **22**, e.g., by dividing the powder mass captured by melt pool **32**, as determined based on data from topology sensor, into the mass flow determined based on data received from PFMS **18**.

[0092] Further, one or more computing devices **12** may determine an overall mass flux using the data received from PFMS **18**, powder flow mass sensor **44**, and/or topology sensor **48**. One or more computing devices **12** then may use the overall mass flux as an input to the control algorithm used to control the powder feed rate output by powder source **42** (see top left of FIG. 7). Additionally, one or more computing devices **12** may determine the position of powder stream **30**, either absolutely within system **10** or relatively with respect to a deposition head.

[0093] Similarly, one or more computing devices **12** may be configured to control energy delivery device **16** to deliver energy **34** to first layer **24** to establish a given heat input (see bottom

left of FIG. 7). For example, one or more computing device **12** may control one or more operating parameters of energy delivery device **16**, such as by maintaining or adjusting an intensity, a pulse rate, a pulse width, or the like; one or more positional parameters related to energy delivery device **16**, such as dwell time at a location, a movement rate relative to first layer **24**, an overlap between adjacent passes of energy **34** across first layer **24**, a pause time between adjacent passes of energy **34** across first layer **24**, or the like to control heat input to system **10** (e.g., to melt pool **32** and component **22**). The positional adjustment may be made to maintain or adjust a relative position of powder stream **30** to melt pool **32**.

[0094] One or more computing devices **12** may be configured to receive data captured by one or more thermal sensors, such as optical system **80** and/or melt pool monitor **15**. One or more computing devices may determine a cooling rate and associated heat from using data from optical system **80** and may determine a heat input into component using a size and/or temperature of melt pool **32** as observed by melt pool monitor **15**. In some examples, one or more computing devices **12** may be configured to capture data from melt pool monitor **15**, and may analyze the captured data to determine a position of a center point of melt pool **32**.

[0095] In some examples, one or more computing devices **12** may, on the basis of the determined positions of powder stream **30** and melt pool **32**, determine the relative position of powder stream **30** to melt pool **32**. The determination of the relative position of powder stream **30** to melt pool **32** may be performed as a validation step on operation of system **10** to prevent overbuild or underbuild, or other deleterious effects of improper alignment of powder delivery device **14** and energy delivery device **16**. With concurrent reference to FIGS. **1** and **2**, in some cases, the powder delivery device and energy delivery device may be parts of deposition head **54**. In such cases, computing device **12**, to determine the relative position of powder stream **30** to melt pool **32**, computing device **12** may compare the position of powder stream central axis **L** to a center point of melt pool **32**. Further, computing device **12** may control the relative position of powder stream **30** to melt pool **32**. For example, computing device **12** may determine that a distance between central axis **L** and the center point melt pool **32** exceeds a threshold distance, and adjust the position of powder delivery device **14** and/or energy delivery device **16** to decrease the distance between central axis **L** of powder stream **30** to melt pool **32** such that the distance falls within a threshold distance. In some examples, computing device **12** may adjust the position of the powder delivery device or the position of the energy delivery device such that central axis **L** passes through, or intersects, a center point of melt pool **32**. In some examples, the center point of melt pool **32** may be a point on the surface of melt pool **32** which is the maximum distance from any edge of melt pool **32**.

[0096] In some examples, as described above, computing device **12** may determine a capture efficiency of powder in powder stream **30** by melt pool **32**. In some examples, computing device **12** may control the relative position of powder stream **30** to melt pool **32** to increase (e.g., maximize) the capture efficiency. While in some cases the capture efficiency may be maximized where powder stream central axis **L** intersects the center point of the melt pool, this is not always the case, as will be further described with respect to FIGS. **8-11**.

[0097] FIGS. **8-11** are conceptual and schematic diagram illustrating a portion of additive manufacturing system **200**. System **200** may be an example of system **10** of FIGS. **1** and **5** or system **100** of FIG. **2**. System **200** includes deposition head **254**, which includes both powder delivery device **214** and energy delivery device **216**. Several additional components, including one or more computing devices, cameras, and sensors as described above with respect to system **10** and system **100** are not illustrated in FIGS. **8-11** for clarity. Components not illustrated in FIGS. **8-11** are described with respect to system **10** of FIGS. **1** and **5**.

[0098] Deposition head **254** includes energy delivery device **216**, which may generate and/or delivery energy **234** to build surface **228** of component **222** to form melt pool **232**. Deposition head **254** includes powder delivery device **214**, which directs powder stream **230** to the melt pool.

Powder in powder stream **230**, at least some of which may be at least partially melted by energy **234** while in flight across working distance WD, is captured by melt pool **232**, and solidifies to form layer **226** on component **222** during the additive manufacturing process. Computing device **12** may cause deposition head **254** to travel along a toolpath, indicated by arrow T in FIGS. **8-11**, and the relative position of powder stream **230** to melt pool **232** may be maintained as deposition head **254** travels along toolpath T to deposit layer **226**.

[0099] Deposition head **254** houses energy delivery device **216**, which in the illustrated example is a laser. Energy delivery device **216** may reside in a cavity within deposition head **254**, and may be supported by one or more adjustable support members **202**. In operation, computing device **12** may control adjustable support members **202** in one or more of the X, Y, or Z directions, via, for example, an electrical connection. Computing device **12** may actuate adjustable support members **202** to adjust the position of energy delivery device **216** within deposition head **254**. In this way, computing device **12** may control the position of melt pool **232** on build surface **228**. In some examples, energy delivery device **216** may include galvanometer **204**, which may include a plurality of mirrors and/or lenses configured to position and shape energy **234** into a beam. Adjustment of galvanometer **204** by computing device **12** may allow for selective tailoring of the position, frequency, polarity, and/or other aspects of energy **234** delivered to build surface **228** to form melt pool **232**.

[0100] Powder travels from powder source **42** through powder delivery device **214** via channels formed in the walls of deposition head **254**, and exits delivery nozzles **256A**, **256B** (collectively, “delivery nozzles **256**”) as powder stream **230A**, **230B** (collectively, “powder stream **230**”). Powder stream **230** defines powder stream central axis L as described above. Powder stream **230** traverses working distance WD between delivery nozzles **256** and build surface **228**. Delivery nozzles **256** may be controlled independent of energy delivery device **216** by computing device **12** to adjust the position of powder stream **230** relative to melt pool **232**. For example, delivery nozzles **256** may direct powder stream **230** towards melt pool **232** at an angle, and the angle may be adjusted by computing device **12**. Similarly, the orifice size or position of delivery nozzles **256** may be adjusted by computing device **12**, in examples where powder delivery device **214** allows for these parameters to be adjusted in situ.

[0101] Computing device **12** may determine, based on captured data that is representative of the position of powder stream **230** and captured data that is representative of melt pool **232**, the relative position of powder stream **230** to melt pool **232**. For example, in computing device **12** may determine central axis L of powder stream **230**, and may also determine center point CP of melt pool **232**. In some examples, computing device **12** may compare the position of powder stream **230** to melt pool **232** by determining a displacement distance D and direction vector between center point CP of melt pool **232** and the point at which powder stream central axis L intersects build surface **228**. Computing device **12** may determine whether displacement distance D exceeds a threshold distance (e.g., less than about **0.1** millimeter, less than about **1** millimeter, less than about **2** millimeters, or the like).

[0102] Responsive to determining that displacement distance D does not exceed a threshold distance, computing device **12** may control deposition head **254** to maintain the relative position of powder stream **230** to melt pool **232** throughout a portion of an additive manufacturing process. Responsive to determining that displacement distance D exceeds a threshold distance, computing device **12** may output a signal indicative of system **200** being out of alignment, may stop the deposition of layer **226**, or may adjust the position of powder delivery device **214** and/or energy delivery device **216** to reduce displacement distance D such that displacement distance D does not exceed the displacement distance threshold.

[0103] FIG. **8** illustrates system **10** in a normal operation. In some examples, system **10** may be set such that powder stream central axis L of powder stream **230** intersects melt pool center point CP of melt pool **232**. Computing device **12** may maintain the relative position of powder stream **230** to

melt pool **232** as deposition head **254** travels along toolpath T to deposit layer **226**. However, some operations may cause dealignment of the relative position of powder stream **230** to melt pool **232**. As illustrated in FIG. **9**, increased velocity of deposition head **254** along toolpath T (indicated by the larger arrow in FIG. **8** compared to FIG. **8**) may cause powder in powder stream **230** to drag behind deposition head **254** when traveling across working distance WD, such that powder stream central axis L is displaced from melt pool center point CP by displacement distance D at build surface **228**. The forces of gravity may have a similar influence, because the force of gravity may cause powder stream **30** to drift off-course where powder stream **230** is directed toward melt pool **232** in a direction that is not parallel to the gravitational force. Other causes of displacement distance D are also considered.

[0104] The displacement between powder stream central axis L may be deleterious to the resulting component **222**. For example, techniques which are performed where displacement distance D is not controlled may result in underbuild and/or overbuild in portions of layer **226**. System **200** may be configured to address this problem by causing, via computing device **12**, adjustment of the relative position of powder stream **230** to melt pool **232**. Adjustment of the relative position of powder stream **230** to melt pool **232** may be accomplished by adjusting, via computing device **12**, the position of energy delivery device **216** (FIG. **10**) and/or adjusting the position of powder delivery device **214** (FIG. **11**). However, in some cases, it may be found that distance D imparts desirable impacts to the additive manufacturing process or resulting component (e.g., increased capture efficiency, reduced spatter from powder entering the melt pool **232**, desired microstructure or porosity of finished component **222**, or the like). In such cases, computing device **12** may control the relative position of powder stream **230** to melt pool **232** such that displacement distance D is controlled (e.g., maintained) throughout at least a portion of the additive-manufacturing process.

[0105] FIG. **10** illustrates an example alignment technique where computing device **12** controls the relative position of powder stream **230** to melt pool **232** by adjustment of the position of energy delivery device **216**. In this example, computing device **212** causes melt pool **232** to move relative to deposition head **254** as it travels along toolpath T by adjustment of galvanometer **204**.

Galvanometer **204** includes a plurality of mirrors and/or lenses, which computing device **12** may control to deflect energy **234** off the path energy **234** was generated on by the laser, such the energy **234** impinges on a different location on build surface **228** than the position of FIG. **8**. Thus, melt pool **232** is formed at a different location relative to powder delivery device **214** and the other components of deposition head **254**. Although illustrated as adjusted solely by control of galvanometer **204**, it is understood that the position of melt pool **232** may also be adjusted by modification of adjustable support members **202** by computing device **12**. In some examples, as illustrated, computing device **12** may adjust the position of melt pool **232** such the displacement distance D is decreased (e.g., eliminated). Thus, system **10** may be configured to account for and control displacement distance D by modification of the relative position of powder stream **230** to melt pool **232** to realign system **10**.

[0106] FIG. **11** illustrates an example alignment technique where computing device **12** controls the relative position of powder stream **230** to melt pool **232** by adjustment of the position of powder delivery device **214**. For example, after determining that the control technique of FIG. **9** results in a capture efficiency that does not meet a threshold capture efficiency for continuing the build under the current settings, computing device **12** may adjust the angle delivery nozzles **256** by angle α . Adjustment of the position of delivery nozzles **256** may cause powder stream central axis L to intersect melt pool center point CP. In some examples, adjustment of the position of powder delivery device **214** by computing device **12** may control the relative position of powder stream **230** to melt pool **232** to increase and/or optimize the capture efficiency.

[0107] The control techniques illustrated in FIGS. **10** and **11** may be used together or separately during an additive manufacturing process to realign or maintain desired control of the relative

position of powder stream **230** to melt pool **232**. Further, the techniques illustrated by FIGS. **10** and **11** may be employed in various degrees during different portions of the manufacture of component **22**. For example, computing device **12** may control delivery nozzles **256** such that angle α has a greater magnitude when deposition is occurring substantially orthogonal to the gravitational force than when deposition is occurring substantially parallel to the gravitational force. As another example, computing device **12** may cause melt pool **232** to move further from a default position when deposition head **254** is traveling faster along toolpath **T** than when deposition head **254** is moving along toolpath **T** at a slower rate.

[0108] FIG. **12** is a flow diagram illustrating an example technique for validating alignment of a powder stream and melt pool according to the present disclosure. The illustrated technique may be performed by system **10** of FIGS. **1** and **5**, and is primarily described as performed by system **10**, but other systems may be used to perform the described techniques, such as system **100** of FIG. **2** or system **200** of FIGS. **8-11**. Furthermore, system **10** and system **100** may be used to perform other techniques.

[0109] The technique of FIG. **12** includes controlling, by computing device **12** of system **10**, deposition of layer **26** on component **22** by additive manufacturing system **10** (**302**). To deposit layer **26**, computing device **12** causes energy delivery device **16** to deliver energy **34** to form melt pool **32** on build surface **28** of component **22**. Computing device **12** then causes powder delivery device **14** to direct powder stream **30** to melt pool **32**. Powder in powder stream **30** is captured by melt pool **32**, and the melt pool and captured powder solidify to form layer **26**.

[0110] Computing device **12** may determine whether powder stream **30** and melt pool **32** are in alignment (**304**). Computing device **12** may store instruction to make the alignment determination base on build progress (e.g., every layer **26**, every completion of a toolpath pattern, or the like) or based on a time increment (e.g., every second, every minute, or the like). In some examples, to determine the position of powder stream **30**, computing device **12** may determine a position of central axis **L** of powder stream **30** using data captured by PFMS **18**. Similarly, computing device **12** may determine a position of melt pool **32** using data captured by MP monitor **15** and/or optical system **80**. MP monitor **15**, optical system **80**, and/or PFMS **18** may use a combination of coaxial and off-axis imaging devices such as cameras.

[0111] With concurrent reference to FIGS. **1**, **5**, and **8-11**, In some examples, to determine the position of melt pool **32**, computing device **12** may determine a position of melt pool center point **CP**. To determine the relative position of powder stream **30** to melt pool **32**, computing device **12** may compare the position of central axis **L** of powder stream **30** to the position of center point **CP** of melt pool **32**. Responsive to determining that displacement distance **D** does not exceed a threshold (“YES” path in FIG. **12**) and/or that the capture efficiency calculated based on data from mass sensor **44** and topology sensor **48** meets a threshold capture efficiency, computing device **12** may cause system **10** to continue the build, and may continue to validate the alignment of powder stream **30** to melt pool **32** to account for changing manufacturing settings or conditions.

[0112] Responsive to determining that displacement distance **D** exceeds a threshold displacement distance and/or that the calculated capture efficiency does not meet a threshold capture efficiency, computing device **12** may adjust the relative position of powder stream **30** to melt pool **32** (**306**). In some examples, computing device **12** may adjust the relative position of powder stream **30** to melt pool **32** by adjusting the position at least one of powder delivery device **14** or energy delivery device **16**.

[0113] In some examples, computing device **12** may receive additional additive manufacturing system parameters and settings as inputs to determine whether, where, and by what magnitude to adjust the position of powder delivery device **14** and energy delivery device **16**. Such additional parameters may include, but are not limited to, at least one of a powder size distribution of powder in powder stream **30**, a beam shape of energy beam **34**, a melt pool shape, size, or depth of melt pool **32**, a powder feed mass flow rate from powder source **42** via mass sensor **44**, a process gas

flow rate, direction, and/or velocity, or the like. In some examples computing device **12** may execute a machine learning algorithm. The machine learning algorithm may be data generated by the determined capture efficiency and the relative position of the powder stream to the melt pool, and may be trained on any or all of the data from the additional parameters or setting of system **10**. Process gases, as described herein, include powder carrier gases, center purge gases, coverage gases, or other gas flows that modify the shape or location of powder stream **30**.

[0114] FIG. **13** is a flow diagram illustrating an example technique for controlling alignment of the relative position of a powder stream to a melt pool according to the present disclosure. The illustrated technique may be performed by system **10** of FIGS. **1** and **5**, and is primarily described as performed by system **10**, but other systems may be used to perform the described techniques, such as system **100** of FIG. **2** or system **200** of FIGS. **8-11**. Furthermore, system **10** and system **100** may be used to perform other techniques.

[0115] Computing device **12** may cause energy delivery device **16** to deliver energy **34** to build surface **28** of additively-manufactured component **22** to form melt pool **32** in build surface **28** of component **22** (**402**). Component **22** may, in some examples, be a gas turbine engine component. In some examples, component **22** may be define a complex geometry not defined by rectilinear polygons. In some cases, energy delivery device may be a laser. Example laser sources include a CO laser, a CO.sub.2 laser, a Nd:YAG laser, or the like. In some examples, energy delivery device **16** may both generate and deliver energy **34**. In some examples, energy **34** may be selected to provide energy with a predetermined wavelength or wavelength spectrum that may be absorbed by component **22** and/or the powder to be added to component **22** during the additive manufacturing technique.

[0116] Computing device **12** may cause powder delivery device **14** to deliver powder stream **30** to melt pool **32** to add material to component **22** (**404**). In some examples, powder stream **30** may be powder entrained in a carrier gas or gases. The powder may include a metal or alloy, such that additively-manufactured component **22** includes a metal or an alloy. In some examples, powder delivery device **14** and energy delivery device **16** may be parts of a common deposition head **54**. Deposition head **54** may travel along toolpath **T** to deposit layer **26** of material on a component during an additive manufacturing process.

[0117] Computing device **12** may receive from powder flow monitoring system (PFMS) **18**, data indicative of a position of powder stream **30** (**406**). PFMS **18** may include one or more cameras which capture image data, and computing device **12** may analyze the captured image data to determine the position of powder stream **30**. In some examples, computing device **12** may determine a position of central axis **L** of powder stream **30**, and may map the position of central axis **L** relative to deposition head **54** (FIG. **2**), or absolutely within system **100** (FIG. **2**).

[0118] Computing device may receive data indicative of a position of melt pool **32** from optical system **80** (**408**). Optical system **80** may include one or more cameras which capture image data, and computing device **12** may analyze the captured image data to determine the position of melt pool **32**. For example, optical system **80** may include a camera disposed on an axis of energy delivery device **16**, and a second camera displaced from the axis of energy delivery device **16** positioned to capture data indicative of the relative position of powder stream **30** to melt pool **32**. In some examples, to determine the position of melt pool **32**, computing device **12** may determine a position of center point **CP** of melt pool **32**.

[0119] Computing device **12** may determine, based on the position of powder stream **30** and the position of melt pool **32**, a relative position of powder stream **30** to melt pool (**410**). In some examples, to determine the relative position of powder stream **30** to melt pool **32**, computing device **12** may compare the position of central axis **L** of powder stream **30** to the position of center point **CP** of melt pool **32**. In some examples, system **10** may additively manufacture component **22** while component **22** is supported by stage **20**. Computing device **12** may adjust the relative position of powder stream **30** to melt pool **32** while component **22** is being additively-

manufactured and mechanically supported by stage 20.

[0120] Computing device 12 may control energy delivery device 16 and powder delivery device 14 based at least partially on the relative position powder stream 30 to melt pool 32 (412). In some examples, computing device 12 may determine whether displacement distance D between central axis L of powder stream 30 and center point CP of melt pool 32 exceeds a threshold distance. Responsive to determining that displacement distance D exceeds a threshold displacement distance D, computing device 12 may adjust relative position of central axis L of powder stream 30 or center point CP of melt pool 32 to decrease displacement distance D such that displacement distance D falls within the threshold distance. To adjust the position of powder stream 30, computing device 12 may adjust the position of powder delivery device 14, for example by manipulation of the angle or position of one or more delivery nozzles 56. Similarly, to adjust the position of melt pool 32, computing device 12 may adjust the position of delivery device 16, for example by manipulation of the position of one or more adjustable support members 202 or galvanometer 204. In some examples, computing device 12 may adjust at least one of the positions of energy delivery device 16 or powder delivery device 14 such that central axis L of powder stream 30 intersects center point CP of melt pool 32.

[0121] In some examples, computing device 12 may determine a capture efficiency of powder in the powder stream 30 by melt pool 32. Based on the determined capture efficiency, computing device 12 may determine an adjustment to the position of one or both of powder delivery device 14 and/or energy delivery device 16. Computing device 12 may control, based on the determined adjustment, powder delivery device 14 and/or energy delivery device 16. Computing device 12 may, determine the adjustment to the position of energy delivery device 16 and/or powder delivery device 14 using a machine learning model that takes the determined captured efficiency as an input. Computing device 12 may further determine a plurality of additional parameters of the additive manufacturing system, and control energy delivery device 16 or powder delivery device 14 based at least partially on the determined additional parameters. Without limitation, the plurality of additional parameters may include a powder size distribution, a beam shape, a melt pool size, a melt pool shape, a powder feed rate, a powder feed mass flow rate, a gas carrier flow rate, a working distance, or the like. For example, one or more of the determined additional parameters may be input into the machine learning model. In some examples, computing device 12 may output, for display at a display device, a graphical representation of the relative position of powder stream 30 to melt pool 32.

[0122] The techniques described in this disclosure may be implemented, at least in part, in hardware, software, firmware, or any combination thereof. For example, various aspects of the described techniques may be implemented within one or more processors, including one or more microprocessors, digital signal processors (DSPs), application specific integrated circuits (ASICs), field programmable gate arrays (FPGAs), or any other equivalent integrated or discrete logic circuitry, as well as any combinations of such components. The term “processor” or “processing circuitry” may generally refer to any of the foregoing logic circuitry, alone or in combination with other logic circuitry, or any other equivalent circuitry. A control unit including hardware may also perform one or more of the techniques of this disclosure.

[0123] Such hardware, software, and firmware may be implemented within the same device or within separate devices to support the various techniques described in this disclosure. In addition, any of the described units, modules or components may be implemented together or separately as discrete but interoperable logic devices. Depiction of different features as modules or units is intended to highlight different functional aspects and does not necessarily imply that such modules or units must be realized by separate hardware, firmware, or software components. Rather, functionality associated with one or more modules or units may be performed by separate hardware, firmware, or software components, or integrated within common or separate hardware, firmware, or software components.

[0124] The techniques described in this disclosure may also be embodied or encoded in an article of manufacture including a computer-readable storage medium encoded with instructions. Instructions embedded or encoded in an article of manufacture including a computer-readable storage medium encoded, may cause one or more programmable processors, or other processors, to implement one or more of the techniques described herein, such as when instructions included or encoded in the computer-readable storage medium are executed by the one or more processors. Computer readable storage media may include random access memory (RAM), read only memory (ROM), programmable read only memory (PROM), erasable programmable read only memory (EPROM), electronically erasable programmable read only memory (EEPROM), flash memory, a hard disk, a compact disc ROM (CD-ROM), a floppy disk, a cassette, magnetic media, optical media, or other computer readable media. In some examples, an article of manufacture may include one or more computer-readable storage media.

[0125] In some examples, a computer-readable storage medium may include a non-transitory medium. The term “non-transitory” may indicate that the storage medium is not embodied in a carrier wave or a propagated signal. In certain examples, a non-transitory storage medium may store data that can, over time, change (e.g., in RAM or cache).

[0126] Various examples have been described. These and other examples are within the scope of the following examples and claims.

[0127] Example 1: An additive manufacturing system includes an energy delivery device configured to deliver energy to a build surface of an additively-manufactured component to form a melt pool in the build surface of the component; a powder delivery device configured to direct a powder stream toward the melt pool; a powder flow monitoring system configured to observe the powder stream; and an optical system configured to observe the melt pool; a computing device configured to: receive, from the powder flow monitoring system, data indicative of a position of the powder stream from the powder flow monitoring system; receive, from the optical system, data indicative of a position of the melt pool; determine, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool; and control, based on the determined relative position of the powder stream to the melt pool, one or both of the powder delivery device and the energy delivery device.

[0128] Example 2: The additive manufacturing system of example 1, wherein: to determine the position of the powder stream, the computing device is configured to determine a position of a central axis of the powder stream; to determine the position of the melt pool, the computing device is configured to determine a position of a center point of the melt pool; and to determine the relative position of the powder stream to the melt pool, the computing device is configured to compare the position of central axis of the powder stream to the position of the center point of the melt pool.

[0129] Example 3: The additive manufacturing system of example 2, wherein the computing device is configured to determine whether a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold distance, and responsive to determining that a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold displacement distance, adjust relative position of the central axis of the powder stream or the center point of the melt pool to decrease the distance between the central axis of the powder stream and the center point of the melt pool to fall to fall within a threshold displacement distance.

[0130] Example 4: The additive manufacturing system of any of examples 2 and 3, wherein the computing device is configured to adjust at least one of the positions of the energy delivery device or the powder delivery device such that the central axis of the powder stream intersects the center point of the melt pool.

[0131] Example 5: The additive manufacturing system of any of examples 1 through 4, wherein, to control the powder delivery device and the energy delivery device, the computing device is

configured to adjust the relative position of the powder stream to the melt pool by adjusting the position at least one of the powder delivery device or the energy delivery device.

[0132] Example 6: The additive manufacturing system of example 5, wherein the computing device is configured to: determine a capture efficiency of powder in the powder stream by the melt pool, determine, based on the determined capture efficiency, an adjustment to one or both of the position of the powder delivery device or the energy delivery device, and control, based on the determined adjustment, the powder delivery device or the energy delivery device.

[0133] Example 7: The additive manufacturing system of example 6, wherein the computing device is configured to determine, using a machine learning model that takes the determined captured efficiency as an input, the adjustment to one or both of the position of the powder delivery device or the energy delivery device.

[0134] Example 8: The additive manufacturing system of any of examples 1 through 7, wherein the powder delivery device and the energy delivery device are parts of a deposition head.

[0135] Example 9: The additive manufacturing system of example 8, wherein: the energy delivery device comprises one or more galvanometers; the energy delivery device is a laser; and the position of the energy delivery device is adjustable by manipulation of the one or more galvanometers.

[0136] Example 10: The additive manufacturing system of any of examples 8 and 9, wherein: the powder delivery device comprises one or more delivery nozzles, and to control the powder delivery device, the computing device is configured to control the angle or the position of the of the one or more delivery nozzles.

[0137] Example 11: The additive manufacturing system of any of examples 1 through 10, wherein: the powder delivery device and the energy delivery device are parts of a deposition head, the central axis of the powder stream is defined by a first point equidistant from a plurality of delivery nozzles at a downstream end of the deposition head and a second point at which powder from each of the plurality of deposition nozzles converges, the deposition head is configured to travel along a toolpath to deposit a layer of material on a component during an additive manufacturing process, the powder stream central axis is displaced along the build surface by a displacement distance from the center point of the melt pool, the computing device is configured to determine the displacement distance, and control the relative position of the powder stream to the melt pool based on the determined displacement distance.

[0138] Example 12: The additive manufacturing system of any of examples 1 through 11, wherein the computing device is further configured to determine a plurality of additional parameters of the additive manufacturing system; wherein the plurality of additional parameters include at least one of a powder size distribution, a beam shape, a melt pool size, a melt pool shape, a powder feed rate, a powder feed mass flow rate, a process gas flow rate, or flow velocity, or flow direction, and control the energy delivery device or the powder delivery device based at least partially on the determined additional parameters.

[0139] Example 13: The additive manufacturing system of any of examples 1 through 12, further comprising the additively manufactured component, wherein the additively manufactured component is a gas turbine engine component.

[0140] Example 14: The additive manufacturing system of any of examples 1 through 13, wherein the computing device is configured to output, for display at a display device, a graphical representation of the relative position of the powder stream to the melt pool.

[0141] Example 15: The additive manufacturing system of any of examples 1 through 14, wherein the optical system includes: a camera disposed on an axis of the energy delivery device, and a second camera displaced from the axis of the energy delivery device positioned to capture data indicative of the relative position of the powder stream to the melt pool, wherein the computing device is configured to adjust the relative position of the powder stream to the melt pool based at least partially on the data captured by the second camera.

[0142] Example 16: The additive manufacturing system of any of examples 1 through 15, wherein

the additive manufacturing system is configured to additively-manufacture the component layer-by-layer while the component is mechanically supported by a stage, and wherein the computing device is configured to adjust the relative position of the powder stream to the melt pool while the component is being additively-manufactured and mechanically supported by the stage.

[0143] Example 17: A method includes delivering, via an energy delivery device, energy to a build surface of an additively-manufactured component to form a melt pool in the build surface of the component; delivering, via a powder delivery device, a powder stream to the melt pool to add material to the component; receiving, from a powder flow monitoring device, data indicative of a position of the powder stream; receiving, from an optical system, data indicative of a position of the melt pool; determining, via a computing device, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool; and controlling, via the computing device, one or both of the energy delivery device and the powder delivery device based at least partially on the relative position of powder stream to the melt pool.

[0144] Example 18: The method of example 17, wherein controlling comprises adjusting, via the computing device, based on the determined relative position of the powder stream and the melt pool, the position of the energy delivery device or the powder delivery device.

[0145] Example 19: The method of any of examples 17 through 18, further includes determining, via the computing device, a central axis of the powder stream to determine the position of the powder stream; determining, via the computing device, a center point of the melt pool to determine the position of the melt pool; and comparing, via the computing device, the central axis of the powder stream to the center point of the melt pool to determine the relative position of the powder stream to the melt pool.

[0146] Example 20: The method of example 19, further comprising determining, via the computing device, whether a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold distance, and responsive to determining that a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold distance, adjusting, via the computing device, the relative position of the central axis of the powder stream or the center point of the melt pool to decrease the distance between the central axis of the powder stream and the center point of the melt pool to fall within a threshold distance.

[0147] Example 21: The method of any of examples 17 through 20, further includes

[0148] determining, via the computing device, a capture efficiency of powder in the powder stream by the melt pool, and adjusting, via the computing device, the relative position of the powder stream or the melt pool to increase the capture efficiency.

Claims

1. An additive manufacturing system comprising: an energy delivery device configured to deliver energy to a build surface of an additively-manufactured component to form a melt pool in the build surface of the component; a powder delivery device configured to direct a powder stream toward the melt pool; a powder flow monitoring system configured to observe the powder stream; and an optical system configured to observe the melt pool; a computing device configured to: receive, from the powder flow monitoring system, data indicative of a position of the powder stream from the powder flow monitoring system; receive, from the optical system, data indicative of a position of the melt pool; determine, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool; and control, based on the determined relative position of the powder stream to the melt pool, one or both of the powder delivery device and the energy delivery device.

2. The additive manufacturing system of claim 1, wherein: to determine the position of the powder stream, the computing device is configured to determine a position of a central axis of the powder stream; to determine the position of the melt pool, the computing device is configured to determine

a position of a center point of the melt pool; and to determine the relative position of the powder stream to the melt pool, the computing device is configured to compare the position of central axis of the powder stream to the position of the center point of the melt pool.

3. The additive manufacturing system of claim 2, wherein the computing device is configured to determine whether a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold distance, and responsive to determining that a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold displacement distance, adjust relative position of the central axis of the powder stream or the center point of the melt pool to decrease the distance between the central axis of the powder stream and the center point of the melt pool to fall within a threshold displacement distance.

4. The additive manufacturing system of claim 2, wherein the computing device is configured to adjust at least one of the positions of the energy delivery device or the powder delivery device such that the central axis of the powder stream intersects the center point of the melt pool.

5. The additive manufacturing system of claim 1, wherein, to control the powder delivery device and the energy delivery device, the computing device is configured to adjust the relative position of the powder stream to the melt pool by adjusting the position at least one of the powder delivery device or the energy delivery device.

6. The additive manufacturing system of claim 5, wherein the computing device is configured to: determine a capture efficiency of powder in the powder stream by the melt pool, determine, based on the determined capture efficiency, an adjustment to one or both of the position of the powder delivery device or the energy delivery device, and control, based on the determined adjustment, the powder delivery device or the energy delivery device.

7. The additive manufacturing system of claim 6, wherein the computing device is configured to determine, using a machine learning model that takes the determined captured efficiency as an input, the adjustment to one or both of the position of the powder delivery device or the energy delivery device.

8. The additive manufacturing system of claim 1, wherein the powder delivery device and the energy delivery device are parts of a deposition head.

9. The additive manufacturing system of claim 8, wherein: the energy delivery device comprises one or more galvanometers; the energy delivery device is a laser; and the position of the energy delivery device is adjustable by manipulation of the one or more galvanometers.

10. The additive manufacturing system of claim 8, wherein: the powder delivery device comprises one or more delivery nozzles, and to control the powder delivery device, the computing device is configured to control the angle or the position of the of the one or more delivery nozzles.

11. The additive manufacturing system of claim 1, wherein: the powder delivery device and the energy delivery device are parts of a deposition head, the central axis of the powder stream is defined by a first point equidistant from a plurality of delivery nozzles at a downstream end of the deposition head and a second point at which powder from each of the plurality of deposition nozzles converges, the deposition head is configured to travel along a toolpath to deposit a layer of material on a component during an additive manufacturing process, the powder stream central axis is displaced along the build surface by a displacement distance from the center point of the melt pool, the computing device is configured to determine the displacement distance, and control the relative position of the powder stream to the melt pool based on the determined displacement distance.

12. The additive manufacturing system of claim 1, wherein the computing device is further configured to determine a plurality of additional parameters of the additive manufacturing system; wherein the plurality of additional parameters include at least one of a powder size distribution, a beam shape, a melt pool size, a melt pool shape, a powder feed rate, a powder feed mass flow rate, a process gas flow rate, or flow velocity, or flow direction, and control the energy delivery device or the powder delivery device based at least partially on the determined additional parameters.

- 13.** The additive manufacturing system of claim 1, further comprising the additively manufactured component, wherein the additively manufactured component is a gas turbine engine component.
- 14.** The additive manufacturing system of claim 1, wherein the optical system includes: a camera disposed on an axis of the energy delivery device, and a second camera displaced from the axis of the energy delivery device positioned to capture data indicative of the relative position of the powder stream to the melt pool, wherein the computing device is configured to adjust the relative position of the powder stream to the melt pool based at least partially on the data captured by the second camera.
- 15.** The additive manufacturing system of claim 1, wherein the additive manufacturing system is configured to additively-manufacture the component layer-by-layer while the component is mechanically supported by a stage, and wherein the computing device is configured to adjust the relative position of the powder stream to the melt pool while the component is being additively-manufactured and mechanically supported by the stage.
- 16.** A method comprising: delivering, via an energy delivery device, energy to a build surface of an additively-manufactured component to form a melt pool in the build surface of the component; delivering, via a powder delivery device, a powder stream to the melt pool to add material to the component; receiving, from a powder flow monitoring device, data indicative of a position of the powder stream; receiving, from an optical system, data indicative of a position of the melt pool; determining, via a computing device, based on the position of the powder stream and the position of the melt pool, a relative position of the powder stream to the melt pool; and controlling, via the computing device, one or both of the energy delivery device and the powder delivery device based at least partially on the relative position of powder stream to the melt pool.
- 17.** The method of claim 16, wherein controlling comprises adjusting, via the computing device, based on the determined relative position of the powder stream and the melt pool, the position of the energy delivery device or the powder delivery device.
- 18.** The method of claim 16, further comprising: determining, via the computing device, a central axis of the powder stream to determine the position of the powder stream; determining, via the computing device, a center point of the melt pool to determine the position of the melt pool; and comparing, via the computing device, the central axis of the powder stream to the center point of the melt pool to determine the relative position of the powder stream to the melt pool.
- 19.** The method of claim 18, further comprising determining, via the computing device, whether a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold distance, and responsive to determining that a distance between the central axis of the powder stream and the center point of the melt pool exceeds a threshold distance, adjusting, via the computing device, the relative position of the central axis of the powder stream or the center point of the melt pool to decrease the distance between the central axis of the powder stream and the center point of the melt pool to fall to fall within a threshold distance.
- 20.** The method of claim 16, further comprising: determining, via the computing device, a capture efficiency of powder in the powder stream by the melt pool, and adjusting, via the computing device, the relative position of the powder stream or the melt pool to increase the capture efficiency.
-