

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12401089

Kind Code

B2

Date of Patent

August 26, 2025

Inventor(s)

Chen; Junzheng et al.

Electrochemical cells with multiple separators, and methods of producing the same

Abstract

Embodiments described herein relate to electrochemical cells with multiple separators, and methods of producing the same. A method of producing an electrochemical cell can include disposing an anode material onto an anode current collector, disposing a first separator on the anode material, disposing a cathode material onto a cathode current collector, disposing a second separator onto the cathode material, and disposing the first separator on the second separator to form the electrochemical cell. The anode material and/or the cathode material can be a semi-solid electrode material including an active material, a conductive material, and a volume of liquid electrolyte. In some embodiments, less than about 10% by volume of the liquid electrolyte evaporates during the forming of the electrochemical cell. In some embodiments, the method can further include wetting the first separator and/or the second separator with an electrolyte solution prior to coupling the first separator to the second separator.

Inventors: Chen; Junzheng (Concord, MA), Ota; Naoki (Lexington, MA), Disko; Jeffry (Lexington, MA), D'Angelo; Anthony (Medford, MA)

Applicant: 24M Technologies, Inc. (Cambridge, MA)

Family ID: 1000008779452

Assignee: 24M Technologies, Inc. (Cambridge, MA)

Appl. No.: 18/777403

Filed: July 18, 2024

Prior Publication Data

Document Identifier

Publication Date

US 20240372214 A1

Nov. 07, 2024

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01M50/414** (20210101); **H01M4/131** (20100101); **H01M4/136** (20100101);
H01M4/1391 (20100101); **H01M4/1397** (20100101); **H01M10/0562** (20100101);
H01M50/403 (20210101); **H01M50/46** (20210101); **H01M50/491** (20210101)

U.S. Cl.:

CPC **H01M50/414** (20210101); **H01M4/131** (20130101); **H01M4/136** (20130101);
H01M4/1391 (20130101); **H01M4/1397** (20130101); **H01M10/0562** (20130101);
H01M50/403 (20210101); **H01M50/46** (20210101); **H01M50/491** (20210101);
H01M2300/0051 (20130101)

Field of Classification Search

CPC: H01M (50/457); H01M (50/46)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3625771	12/1970	Arrance et al.	N/A	N/A
3647554	12/1971	Arrance et al.	N/A	N/A
3703413	12/1971	Arrance	N/A	N/A
4338177	12/1981	Withers et al.	N/A	N/A
4342637	12/1981	Withers et al.	N/A	N/A
4670110	12/1986	Withers et al.	N/A	N/A
4711719	12/1986	Leenaars et al.	N/A	N/A
4826743	12/1988	Nazri	N/A	N/A
4916033	12/1989	Gourdine	N/A	N/A
5162175	12/1991	Visco et al.	N/A	N/A
5194341	12/1992	Bagley et al.	N/A	N/A
5314765	12/1993	Bates	N/A	N/A
5326391	12/1993	Anderson et al.	N/A	N/A
5340669	12/1993	Chaloner-Gill et al.	N/A	N/A
5350645	12/1993	Lake et al.	N/A	N/A
5415954	12/1994	Gauthier et al.	N/A	N/A
5418091	12/1994	Gozdz et al.	N/A	N/A
5439760	12/1994	Howard et al.	N/A	N/A
5549717	12/1995	Takeuchi et al.	N/A	N/A
5569520	12/1995	Bates	N/A	N/A
5597659	12/1996	Morigaki et al.	N/A	N/A
5691005	12/1996	Morigaki et al.	N/A	N/A
5731104	12/1997	Ventura et al.	N/A	N/A
5778515	12/1997	Menon	N/A	N/A

5824434	12/1997	Kawakami et al.	N/A	N/A
5840087	12/1997	Gozdz et al.	N/A	N/A
5882721	12/1998	Delnick	N/A	N/A
5888431	12/1998	Tonar et al.	N/A	N/A
5894656	12/1998	Menon et al.	N/A	N/A
5948464	12/1998	Delnick	N/A	N/A
5983488	12/1998	Erickson et al.	N/A	N/A
6148503	12/1999	Delnick et al.	N/A	N/A
6153337	12/1999	Carlson et al.	N/A	N/A
6156190	12/1999	Xia et al.	N/A	N/A
6162563	12/1999	Miura et al.	N/A	N/A
6172795	12/2000	Carlson	N/A	N/A
6183901	12/2000	Ying et al.	N/A	N/A
6190426	12/2000	Thibault et al.	N/A	N/A
6194098	12/2000	Ying et al.	N/A	N/A
6210831	12/2000	Gorkovenko et al.	N/A	N/A
6224846	12/2000	Hurlburt et al.	N/A	N/A
6268087	12/2000	Kim et al.	N/A	N/A
6277514	12/2000	Ying et al.	N/A	N/A
6277981	12/2000	Tu et al.	N/A	N/A
6287720	12/2000	Yamashita et al.	N/A	N/A
6306545	12/2000	Carlson et al.	N/A	N/A
6328770	12/2000	Gozdz	N/A	N/A
6344293	12/2001	Geronov	N/A	N/A
6358397	12/2001	Lyublinski	N/A	N/A
6387564	12/2001	Yamashita et al.	N/A	N/A
6406814	12/2001	Gorkovenko et al.	N/A	N/A
6410182	12/2001	Ying et al.	N/A	N/A
6423444	12/2001	Ying et al.	N/A	N/A
6423447	12/2001	Ohsaki et al.	N/A	N/A
6432586	12/2001	Zhang	N/A	N/A
6436583	12/2001	Mikhaylik	N/A	N/A
6444344	12/2001	Saito et al.	N/A	N/A
6451484	12/2001	Han et al.	N/A	N/A
6488721	12/2001	Carlson	N/A	N/A
6495292	12/2001	Yen	N/A	N/A
6497780	12/2001	Carlson	N/A	N/A
6589692	12/2002	Takami	N/A	N/A
6679926	12/2003	Kajiura et al.	N/A	N/A
6682856	12/2003	Watanabe et al.	N/A	N/A
6723467	12/2003	Yoshida et al.	N/A	N/A
6724512	12/2003	Carlson et al.	N/A	N/A
6811928	12/2003	Aihara et al.	N/A	N/A
6846435	12/2004	Bohnen et al.	N/A	N/A
6883347	12/2004	Ayub	N/A	N/A
6946218	12/2004	Crouch, Jr. et al.	N/A	N/A
6962182	12/2004	Cordonnier et al.	N/A	N/A
6991874	12/2005	Möhwald et al.	N/A	N/A
7014948	12/2005	Lee et al.	N/A	N/A
7029796	12/2005	Choi et al.	N/A	N/A

7066971	12/2005	Carlson	N/A	N/A
7070632	12/2005	Visco et al.	N/A	N/A
7081142	12/2005	Carlson	N/A	N/A
7115339	12/2005	Nakajima et al.	N/A	N/A
7135250	12/2005	Sasaki et al.	N/A	N/A
7160603	12/2006	Carlson	N/A	N/A
7378185	12/2007	Fujikawa et al.	N/A	N/A
7396612	12/2007	Ohata et al.	N/A	N/A
7402184	12/2007	Ikuta et al.	N/A	N/A
7419743	12/2007	Fujikawa et al.	N/A	N/A
7422825	12/2007	Inoue et al.	N/A	N/A
7470488	12/2007	Lee et al.	N/A	N/A
7560193	12/2008	Ikuta et al.	N/A	N/A
7575606	12/2008	Fukumoto et al.	N/A	N/A
7595130	12/2008	Kawabata et al.	N/A	N/A
7638230	12/2008	Fujita et al.	N/A	N/A
7638241	12/2008	Lee et al.	N/A	N/A
7662517	12/2009	Lee et al.	N/A	N/A
7674559	12/2009	Min et al.	N/A	N/A
7682740	12/2009	Yong et al.	N/A	N/A
7682751	12/2009	Kato et al.	N/A	N/A
7687202	12/2009	Nishino et al.	N/A	N/A
7695870	12/2009	Park et al.	N/A	N/A
7704641	12/2009	Yong et al.	N/A	N/A
7709140	12/2009	Hennige et al.	N/A	N/A
7709152	12/2009	Kim et al.	N/A	N/A
7709153	12/2009	Lee et al.	N/A	N/A
7745042	12/2009	Fujino et al.	N/A	N/A
7745050	12/2009	Kajita et al.	N/A	N/A
7754375	12/2009	Fujikawa et al.	N/A	N/A
7754377	12/2009	Ohata et al.	N/A	N/A
7758998	12/2009	Ohata et al.	N/A	N/A
7759004	12/2009	Ikuta et al.	N/A	N/A
7811700	12/2009	Hennige et al.	N/A	N/A
7816038	12/2009	Ohata et al.	N/A	N/A
7829242	12/2009	Hörpel et al.	N/A	N/A
7981548	12/2010	Mimura	N/A	N/A
8076027	12/2010	Honda et al.	N/A	N/A
8277981	12/2011	Kim et al.	N/A	N/A
8574743	12/2012	Kim et al.	N/A	N/A
8722226	12/2013	Chiang et al.	N/A	N/A
8722227	12/2013	Chiang et al.	N/A	N/A
8778552	12/2013	Chiang et al.	N/A	N/A
8883347	12/2013	Baba et al.	N/A	N/A
8993159	12/2014	Chiang et al.	N/A	N/A
9070954	12/2014	Carlson et al.	N/A	N/A
9153833	12/2014	Chiang et al.	N/A	N/A
9178200	12/2014	Bazzarella et al.	N/A	N/A
9180412	12/2014	Jo et al.	N/A	N/A
9184464	12/2014	Chiang et al.	N/A	N/A

9203092	12/2014	Slocum et al.	N/A	N/A
9293781	12/2015	Chiang et al.	N/A	N/A
9350009	12/2015	Lim et al.	N/A	N/A
9362583	12/2015	Chiang et al.	N/A	N/A
9385392	12/2015	Chiang et al.	N/A	N/A
9401501	12/2015	Bazzarella et al.	N/A	N/A
9437864	12/2015	Tan et al.	N/A	N/A
9484569	12/2015	Doherty et al.	N/A	N/A
9509176	12/2015	Carter et al.	N/A	N/A
9583780	12/2016	Chiang et al.	N/A	N/A
9614231	12/2016	Carter et al.	N/A	N/A
9786944	12/2016	Chiang et al.	N/A	N/A
9812674	12/2016	Bazzarella et al.	N/A	N/A
9825280	12/2016	Chiang et al.	N/A	N/A
9831518	12/2016	Chiang et al.	N/A	N/A
9831519	12/2016	Chiang et al.	N/A	N/A
9831522	12/2016	Tan et al.	N/A	N/A
10115970	12/2017	Ota et al.	N/A	N/A
10122044	12/2017	Tan et al.	N/A	N/A
10153651	12/2017	Taylor et al.	N/A	N/A
10181587	12/2018	Ota et al.	N/A	N/A
10230128	12/2018	Chiang et al.	N/A	N/A
10236518	12/2018	Chiang et al.	N/A	N/A
10411310	12/2018	Chiang et al.	N/A	N/A
10483582	12/2018	Chiang et al.	N/A	N/A
10497935	12/2018	Ota et al.	N/A	N/A
10522870	12/2018	Tan et al.	N/A	N/A
10566581	12/2019	Bazzarella et al.	N/A	N/A
10566603	12/2019	Slocum et al.	N/A	N/A
10593952	12/2019	Ota et al.	N/A	N/A
10601239	12/2019	Taylor et al.	N/A	N/A
10637038	12/2019	Zagars et al.	N/A	N/A
10734672	12/2019	Chen et al.	N/A	N/A
10777852	12/2019	Woodford et al.	N/A	N/A
10854869	12/2019	Bazzarella et al.	N/A	N/A
10886521	12/2020	Zagars et al.	N/A	N/A
10910858	12/2020	Taylor et al.	N/A	N/A
10957940	12/2020	Tan et al.	N/A	N/A
10964973	12/2020	Tan et al.	N/A	N/A
11005087	12/2020	Ota et al.	N/A	N/A
11018365	12/2020	Chiang et al.	N/A	N/A
11024903	12/2020	Ota et al.	N/A	N/A
11069888	12/2020	Liu et al.	N/A	N/A
11094487	12/2020	Lawrence et al.	N/A	N/A
11094976	12/2020	Chiang et al.	N/A	N/A
11121437	12/2020	Bazzarella et al.	N/A	N/A
11139467	12/2020	Zagars et al.	N/A	N/A
11145909	12/2020	Chiang et al.	N/A	N/A
11309531	12/2021	Slocum et al.	N/A	N/A
11316156	12/2021	Woo et al.	N/A	N/A

11342567	12/2021	Chiang et al.	N/A	N/A
11394023	12/2021	Ofer et al.	N/A	N/A
11394049	12/2021	Tan et al.	N/A	N/A
11462722	12/2021	Aranami et al.	N/A	N/A
11469065	12/2021	Lawrence et al.	N/A	N/A
11476551	12/2021	Tyler et al.	N/A	N/A
11552368	12/2022	Holman et al.	N/A	N/A
11575146	12/2022	Taylor et al.	N/A	N/A
11594793	12/2022	Bazzarella et al.	N/A	N/A
11611061	12/2022	Zagars et al.	N/A	N/A
11631920	12/2022	Bazzarella et al.	N/A	N/A
11646437	12/2022	Bazzarella et al.	N/A	N/A
11652203	12/2022	Zagars et al.	N/A	N/A
11742525	12/2022	Aranami et al.	N/A	N/A
11749804	12/2022	Chen et al.	N/A	N/A
11757129	12/2022	Tan et al.	N/A	N/A
11764353	12/2022	Ota et al.	N/A	N/A
11799085	12/2022	Chae et al.	N/A	N/A
11804595	12/2022	Ota et al.	N/A	N/A
11811119	12/2022	Chiang et al.	N/A	N/A
11831026	12/2022	Ota et al.	N/A	N/A
11855250	12/2022	Taylor et al.	N/A	N/A
11876194	12/2023	Chiang et al.	N/A	N/A
11888144	12/2023	Slocum et al.	N/A	N/A
11909077	12/2023	Chiang et al.	N/A	N/A
11942654	12/2023	Bazzarella et al.	N/A	N/A
11961990	12/2023	Ota et al.	N/A	N/A
11984564	12/2023	Chen	N/A	N/A
12009551	12/2023	Bazzarella et al.	N/A	N/A
12068486	12/2023	Lawrence et al.	N/A	N/A
2001/0000485	12/2000	Ying et al.	N/A	N/A
2001/0038938	12/2000	Takahashi et al.	N/A	N/A
2001/0053475	12/2000	Ying et al.	N/A	N/A
2002/0092155	12/2001	Carlson et al.	N/A	N/A
2002/0141029	12/2001	Carlson et al.	N/A	N/A
2003/0003363	12/2002	Daido et al.	N/A	N/A
2003/0003369	12/2002	Dai	N/A	N/A
2003/0035995	12/2002	Ohsaki et al.	N/A	N/A
2003/0059675	12/2002	Sasaki et al.	N/A	N/A
2003/0118910	12/2002	Carlson	N/A	N/A
2003/0124429	12/2002	Okada et al.	N/A	N/A
2003/0171784	12/2002	Dodd et al.	N/A	N/A
2004/0038090	12/2003	Faris	N/A	N/A
2004/0043295	12/2003	Rodriguez et al.	N/A	N/A
2004/0058246	12/2003	Choi et al.	N/A	N/A
2004/0175626	12/2003	Dasgupta et al.	N/A	N/A
2004/0185335	12/2003	Carlson	N/A	N/A
2004/0188880	12/2003	Bauer et al.	N/A	N/A
2004/0241540	12/2003	Tsutsumi et al.	N/A	N/A
2005/0022370	12/2004	Fu et al.	N/A	N/A

2005/0026037	12/2004	Riley et al.	N/A	N/A
2005/0221190	12/2004	Sudano et al.	N/A	N/A
2005/0255345	12/2004	Gerritse et al.	N/A	N/A
2005/0255769	12/2004	Henninge et al.	N/A	N/A
2005/0266305	12/2004	Ohata et al.	N/A	N/A
2006/0008698	12/2005	Kim et al.	N/A	N/A
2006/0127753	12/2005	Nakashima et al.	N/A	N/A
2006/0172158	12/2005	Min et al.	N/A	N/A
2006/0172185	12/2005	Mimura	N/A	N/A
2006/0177732	12/2005	Visco et al.	N/A	N/A
2006/0222954	12/2005	Skotheim et al.	N/A	N/A
2006/0275661	12/2005	Kim et al.	N/A	N/A
2007/0009803	12/2006	Kim et al.	N/A	N/A
2007/0065714	12/2006	Hambitzer et al.	N/A	N/A
2007/0108120	12/2006	Carlson	N/A	N/A
2007/0110990	12/2006	Carlson	N/A	N/A
2007/0111070	12/2006	Carlson	N/A	N/A
2007/0178384	12/2006	Kajita et al.	N/A	N/A
2007/0184350	12/2006	Kim et al.	N/A	N/A
2007/0189959	12/2006	Carlson et al.	N/A	N/A
2007/0190408	12/2006	Inoue et al.	N/A	N/A
2007/0204458	12/2006	Fujita et al.	N/A	N/A
2007/0243460	12/2006	Carlson et al.	N/A	N/A
2007/0269714	12/2006	Watanabe et al.	N/A	N/A
2007/0275298	12/2006	Igoris et al.	N/A	N/A
2008/0032197	12/2007	Horpel et al.	N/A	N/A
2008/0160412	12/2007	Kasamatsu et al.	N/A	N/A
2008/0166202	12/2007	Dunlap et al.	N/A	N/A
2008/0193845	12/2007	Muraoka et al.	N/A	N/A
2008/0285208	12/2007	Sung et al.	N/A	N/A
2009/0011337	12/2008	Kajita et al.	N/A	N/A
2009/0017380	12/2008	Honda et al.	N/A	N/A
2009/0029261	12/2008	Thomas-Alyea et al.	N/A	N/A
2009/0067119	12/2008	Katayama et al.	N/A	N/A
2009/0087728	12/2008	Less et al.	N/A	N/A
2009/0098457	12/2008	Kwon et al.	N/A	N/A
2009/0155676	12/2008	Zhamu et al.	N/A	N/A
2009/0155678	12/2008	Less et al.	N/A	N/A
2009/0197183	12/2008	Kato	N/A	N/A
2009/0202912	12/2008	Baba et al.	N/A	N/A
2009/0246631	12/2008	Hojo et al.	N/A	N/A
2009/0246636	12/2008	Chiang et al.	N/A	N/A
2009/0269489	12/2008	Hennige et al.	N/A	N/A
2009/0290288	12/2008	Mitchell et al.	N/A	N/A
2009/0311587	12/2008	Best et al.	N/A	N/A
2010/0003592	12/2009	Baba et al.	N/A	N/A
2010/0003595	12/2009	Issaev et al.	N/A	N/A
2010/0047671	12/2009	Chiang et al.	N/A	N/A
2010/0055370	12/2009	Diehl et al.	N/A	N/A
2010/0104817	12/2009	Carlson	N/A	N/A

2010/0175245	12/2009	Do et al.	N/A	N/A
2010/0261065	12/2009	Babinec et al.	N/A	N/A
2010/0285352	12/2009	Juzkow et al.	N/A	N/A
2010/0323264	12/2009	Chiang et al.	N/A	N/A
2011/0052987	12/2010	Katayama et al.	N/A	N/A
2011/0097623	12/2010	Marinis, Jr. et al.	N/A	N/A
2011/0189520	12/2010	Carter et al.	N/A	N/A
2011/0200848	12/2010	Chiang et al.	N/A	N/A
2011/0228385	12/2010	Avison et al.	N/A	N/A
2011/0274948	12/2010	Duduta et al.	N/A	N/A
2011/0281171	12/2010	Yong et al.	N/A	N/A
2012/0028129	12/2011	Furuya	N/A	N/A
2012/0050848	12/2011	Carlson et al.	N/A	N/A
2012/0069429	12/2011	Barrett et al.	N/A	N/A
2012/0107680	12/2011	Amiruddin et al.	N/A	N/A
2012/0115029	12/2011	Carlson	N/A	N/A
2012/0135257	12/2011	Carlson et al.	N/A	N/A
2012/0141877	12/2011	Choi et al.	N/A	N/A
2012/0164499	12/2011	Chiang et al.	N/A	N/A
2012/0189898	12/2011	Wakizaka et al.	N/A	N/A
2012/0231321	12/2011	Huang et al.	N/A	N/A
2012/0258348	12/2011	Hayakawa et al.	N/A	N/A
2013/0055559	12/2012	Slocum et al.	N/A	N/A
2013/0065122	12/2012	Chiang et al.	N/A	N/A
2013/0089770	12/2012	Nishikawa	N/A	N/A
2013/0149613	12/2012	Yoshikawa et al.	N/A	N/A
2013/0171500	12/2012	Xu et al.	N/A	N/A
2013/0260207	12/2012	Uemura	N/A	N/A
2013/0309547	12/2012	Bazzarella et al.	N/A	N/A
2013/0323542	12/2012	Wijayawardhana et al.	N/A	N/A
2013/0337319	12/2012	Doherty et al.	N/A	N/A
2013/0337349	12/2012	Brost et al.	N/A	N/A
2013/0344367	12/2012	Chiang et al.	N/A	N/A
2014/0004437	12/2013	Slocum et al.	N/A	N/A
2014/0030623	12/2013	Chiang et al.	N/A	N/A
2014/0039710	12/2013	Carter et al.	N/A	N/A
2014/0065464	12/2013	Masarapu et al.	N/A	N/A
2014/0154546	12/2013	Carter et al.	N/A	N/A
2014/0170464	12/2013	Iwase	N/A	N/A
2014/0170524	12/2013	Chiang et al.	N/A	N/A
2014/0248521	12/2013	Chiang et al.	N/A	N/A
2014/0315084	12/2013	Liu et al.	N/A	N/A
2014/0315097	12/2013	Tan et al.	N/A	N/A
2015/0024279	12/2014	Tan et al.	N/A	N/A
2015/0030933	12/2014	Goetzen et al.	N/A	N/A
2015/0056426	12/2014	Grouchko et al.	N/A	N/A
2015/0129081	12/2014	Chiang et al.	N/A	N/A
2015/0140371	12/2014	Slocum	N/A	N/A
2015/0162586	12/2014	Fleischmann et al.	N/A	N/A

2015/0171398	12/2014	Roumi	N/A	N/A
2015/0171406	12/2014	Bazzarella et al.	N/A	N/A
2015/0249249	12/2014	Ortega et al.	N/A	N/A
2015/0280267	12/2014	Chiang et al.	N/A	N/A
2015/0295272	12/2014	Chiang et al.	N/A	N/A
2015/0299551	12/2014	Ota et al.	N/A	N/A
2015/0340676	12/2014	Schmidhauser et al.	N/A	N/A
2015/0357626	12/2014	Holman et al.	N/A	N/A
2015/0364790	12/2014	Yonehara et al.	N/A	N/A
2016/0006081	12/2015	Eaglesham et al.	N/A	N/A
2016/0013461	12/2015	Mizuno et al.	N/A	N/A
2016/0013507	12/2015	Chiang et al.	N/A	N/A
2016/0054590	12/2015	Flitsch et al.	N/A	N/A
2016/0056437	12/2015	Huang et al.	N/A	N/A
2016/0056490	12/2015	Chiang et al.	N/A	N/A
2016/0056491	12/2015	Chiang et al.	N/A	N/A
2016/0093884	12/2015	Cui et al.	N/A	N/A
2016/0105042	12/2015	Taylor et al.	N/A	N/A
2016/0126543	12/2015	Ota et al.	N/A	N/A
2016/0133916	12/2015	Zagars et al.	N/A	N/A
2016/0141579	12/2015	Seok et al.	N/A	N/A
2016/0141621	12/2015	Negishi et al.	N/A	N/A
2016/0190536	12/2015	Park et al.	N/A	N/A
2016/0190544	12/2015	Slocum et al.	N/A	N/A
2016/0218375	12/2015	Chiang et al.	N/A	N/A
2016/0268621	12/2015	Chiang et al.	N/A	N/A
2016/0308218	12/2015	Ota et al.	N/A	N/A
2016/0344006	12/2015	Ota et al.	N/A	N/A
2016/0372784	12/2015	Hayner et al.	N/A	N/A
2016/0372802	12/2015	Chiang et al.	N/A	N/A
2017/0018798	12/2016	Tan et al.	N/A	N/A
2017/0025646	12/2016	Ota et al.	N/A	N/A
2017/0025674	12/2016	Tan et al.	N/A	N/A
2017/0033389	12/2016	Chiang et al.	N/A	N/A
2017/0033390	12/2016	Chiang et al.	N/A	N/A
2017/0077464	12/2016	Bazzarella et al.	N/A	N/A
2017/0098857	12/2016	Carlson et al.	N/A	N/A
2017/0149088	12/2016	Ueno et al.	N/A	N/A
2017/0162863	12/2016	Doherty et al.	N/A	N/A
2017/0187078	12/2016	Keates et al.	N/A	N/A
2017/0214034	12/2016	Ota et al.	N/A	N/A
2017/0237111	12/2016	Holman et al.	N/A	N/A
2017/0237112	12/2016	Holman et al.	N/A	N/A
2017/0271638	12/2016	Xu et al.	N/A	N/A
2017/0288281	12/2016	Chiang et al.	N/A	N/A
2017/0324073	12/2016	Herle	N/A	N/A
2018/0034090	12/2017	Chiang et al.	N/A	N/A
2018/0108893	12/2017	Yang	N/A	N/A
2018/0175428	12/2017	Chiang et al.	N/A	N/A
2018/0175445	12/2017	Tan et al.	N/A	N/A

2018/0219250	12/2017	Delobel et al.	N/A	N/A
2018/0233708	12/2017	Bazzarella et al.	N/A	N/A
2018/0233722	12/2017	Holman et al.	N/A	N/A
2018/0287220	12/2017	Woodford et al.	N/A	N/A
2019/0036101	12/2018	Tyler et al.	N/A	N/A
2019/0044196	12/2018	Kang et al.	N/A	N/A
2019/0058184	12/2018	Bazzarella et al.	N/A	N/A
2019/0181496	12/2018	Visco et al.	N/A	N/A
2019/0245242	12/2018	Tan et al.	N/A	N/A
2019/0267598	12/2018	Xu et al.	N/A	N/A
2019/0319460	12/2018	Taylor et al.	N/A	N/A
2019/0326562	12/2018	Ota et al.	N/A	N/A
2019/0348705	12/2018	Chen	N/A	H01M 50/449
2019/0355998	12/2018	Chiang et al.	N/A	N/A
2019/0363351	12/2018	Ota et al.	N/A	N/A
2019/0393477	12/2018	Lawrence et al.	N/A	N/A
2020/0014025	12/2019	Zagars et al.	N/A	N/A
2020/0044296	12/2019	Chiang et al.	N/A	N/A
2020/0106094	12/2019	Ota et al.	N/A	N/A
2020/0144686	12/2019	Jang et al.	N/A	N/A
2020/0161688	12/2019	Chiang et al.	N/A	N/A
2020/0207237	12/2019	Zuo et al.	N/A	N/A
2020/0220118	12/2019	Bazzarella et al.	N/A	N/A
2020/0220204	12/2019	Tan et al.	N/A	N/A
2020/0259338	12/2019	Taylor et al.	N/A	N/A
2020/0266407	12/2019	Honda et al.	N/A	N/A
2020/0266479	12/2019	Hupfer et al.	N/A	N/A
2020/0303707	12/2019	Zhou et al.	N/A	N/A
2020/0321597	12/2019	Zagars et al.	N/A	N/A
2020/0321601	12/2019	Slocum et al.	N/A	N/A
2020/0358129	12/2019	Chen et al.	N/A	N/A
2020/0395069	12/2019	Tang et al.	N/A	N/A
2020/0395583	12/2019	Carlson et al.	N/A	N/A
2020/0411825	12/2019	Bazzarella et al.	N/A	N/A
2021/0080364	12/2020	Lee et al.	N/A	N/A
2021/0091366	12/2020	Bazzarella et al.	N/A	N/A
2021/0167351	12/2020	Zagars et al.	N/A	N/A
2021/0226192	12/2020	Aranami et al.	N/A	N/A
2021/0249678	12/2020	Chiang et al.	N/A	N/A
2021/0249695	12/2020	Aranami et al.	N/A	N/A
2021/0257679	12/2020	Tour et al.	N/A	N/A
2021/0265631	12/2020	Chen et al.	N/A	N/A
2021/0273268	12/2020	Yu et al.	N/A	N/A
2021/0296733	12/2020	Carlson et al.	N/A	N/A
2021/0359527	12/2020	Taylor et al.	N/A	N/A
2021/0376380	12/2020	Tan et al.	N/A	N/A
2021/0384516	12/2020	Lawrence et al.	N/A	N/A
2022/0006157	12/2021	Nakazawa	N/A	H01M 50/417

2022/0021019	12/2021	Tan et al.	N/A	N/A
2022/0029207	12/2021	Chiang et al.	N/A	N/A
2022/0037749	12/2021	Bazzarella et al.	N/A	N/A
2022/0052403	12/2021	Chen et al.	N/A	N/A
2022/0077445	12/2021	Ota et al.	N/A	N/A
2022/0085440	12/2021	Ota et al.	N/A	N/A
2022/0093929	12/2021	Chen et al.	N/A	N/A
2022/0115710	12/2021	Zagars et al.	N/A	N/A
2022/0172916	12/2021	Lawrence et al.	N/A	N/A
2022/0173446	12/2021	Chiang et al.	N/A	N/A
2022/0200306	12/2021	Kusachi et al.	N/A	N/A
2022/0231274	12/2021	Zagars et al.	N/A	N/A
2022/0238923	12/2021	Chen et al.	N/A	N/A
2022/0263104	12/2021	Chiang et al.	N/A	N/A
2022/0263193	12/2021	Chen et al.	N/A	N/A
2022/0278427	12/2021	Lawrence et al.	N/A	N/A
2022/0285669	12/2021	Doherty et al.	N/A	N/A
2022/0294079	12/2021	Zhang et al.	N/A	N/A
2022/0299572	12/2021	Aoki	N/A	N/A
2022/0344775	12/2021	Carlson et al.	N/A	N/A
2022/0344776	12/2021	Carlson	N/A	N/A
2022/0352597	12/2021	Chen et al.	N/A	N/A
2022/0352598	12/2021	Avison et al.	N/A	N/A
2023/0018078	12/2022	Slocum et al.	N/A	N/A
2023/0022329	12/2022	Chen et al.	N/A	N/A
2023/0085181	12/2022	Tan et al.	N/A	N/A
2023/0090853	12/2022	Tyler et al.	N/A	N/A
2023/0098274	12/2022	Carlson et al.	N/A	N/A
2023/0118961	12/2022	Chen et al.	N/A	N/A
2023/0133464	12/2022	Ota et al.	N/A	N/A
2023/0170169	12/2022	Lawrence et al.	N/A	N/A
2023/0178707	12/2022	Aranami et al.	N/A	N/A
2023/0238562	12/2022	Kusachi et al.	N/A	N/A
2023/0261247	12/2022	Ju et al.	N/A	N/A
2023/0282906	12/2022	Chen et al.	N/A	N/A
2023/0291063	12/2022	Holman et al.	N/A	N/A
2023/0307803	12/2022	Bazzarella et al.	N/A	N/A
2023/0327068	12/2022	Tyler et al.	N/A	N/A
2023/0327077	12/2022	Zagars et al.	N/A	N/A
2023/0327178	12/2022	Taylor et al.	N/A	N/A
2023/0335748	12/2022	Chen et al.	N/A	N/A
2023/0352755	12/2022	Aragon et al.	N/A	N/A
2023/0369603	12/2022	Ota et al.	N/A	N/A
2023/0369719	12/2022	Bazzarella et al.	N/A	N/A
2023/0378512	12/2022	Bazzarella et al.	N/A	N/A
2023/0395771	12/2022	Zagars et al.	N/A	N/A
2023/0411695	12/2022	Narita et al.	N/A	N/A
2024/0039001	12/2023	Kusachi et al.	N/A	N/A
2024/0039120	12/2023	Carlson	N/A	N/A
2024/0047689	12/2023	Hartzog et al.	N/A	N/A

2024/0047772	12/2023	Hartzog et al.	N/A	N/A
2024/0055702	12/2023	Ota et al.	N/A	N/A
2024/0063417	12/2023	Chiang et al.	N/A	N/A
2024/0079647	12/2023	Tan et al.	N/A	N/A
2024/0088355	12/2023	Ota et al.	N/A	N/A
2024/0106003	12/2023	Aranami et al.	N/A	N/A
2024/0128541	12/2023	Nematollahi	N/A	N/A
2024/0178502	12/2023	Ota	N/A	N/A
2024/0204264	12/2023	Chen	N/A	N/A
2024/0204288	12/2023	Nematollahi	N/A	N/A
2024/0213572	12/2023	Nematollahi	N/A	N/A
2024/0234705	12/2023	Ota et al.	N/A	N/A
2024/0274855	12/2023	Chiang et al.	N/A	N/A
2024/0304942	12/2023	Patel et al.	N/A	N/A
2025/0054939	12/2024	Aranami	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2605874	12/2006	CA	N/A
2886154	12/2013	CA	N/A
1285084	12/2000	CN	N/A
1492523	12/2003	CN	N/A
1167163	12/2003	CN	N/A
1175505	12/2003	CN	N/A
101796668	12/2009	CN	N/A
101946344	12/2010	CN	N/A
102242464	12/2010	CN	N/A
102437302	12/2011	CN	N/A
102460772	12/2011	CN	N/A
102640329	12/2011	CN	N/A
102769116	12/2011	CN	N/A
102959765	12/2012	CN	N/A
101796668	12/2012	CN	N/A
103262305	12/2012	CN	N/A
103282408	12/2012	CN	N/A
103283060	12/2012	CN	N/A
102640329	12/2014	CN	N/A
105247703	12/2015	CN	N/A
0143562	12/1984	EP	N/A
0523840	12/1992	EP	N/A
0600718	12/1993	EP	N/A
0523840	12/1995	EP	N/A
0814520	12/1996	EP	N/A
0836238	12/1997	EP	N/A
0848435	12/1997	EP	N/A
0875950	12/1997	EP	N/A
0892449	12/1998	EP	N/A
0600718	12/1999	EP	N/A
1156544	12/2000	EP	N/A

0836238	12/2004	EP	N/A
0848435	12/2006	EP	N/A
3133671	12/2016	EP	N/A
4117104	12/2022	EP	N/A
3007207	12/2013	FR	N/A
S4610339	12/1970	JP	N/A
H05283108	12/1992	JP	N/A
H0614077	12/1993	JP	N/A
H06140077	12/1993	JP	N/A
H06275313	12/1993	JP	N/A
H087895	12/1995	JP	N/A
H08255615	12/1995	JP	N/A
H0927343	12/1996	JP	N/A
H10214639	12/1997	JP	N/A
H11233144	12/1998	JP	N/A
2000011986	12/1999	JP	N/A
2000323129	12/1999	JP	N/A
2001143690	12/2000	JP	N/A
2002042882	12/2001	JP	N/A
2002203542	12/2001	JP	N/A
2002532852	12/2001	JP	N/A
2003517418	12/2002	JP	N/A
2003223926	12/2002	JP	N/A
2004119367	12/2003	JP	N/A
2005022674	12/2004	JP	N/A
2005190785	12/2004	JP	N/A
2005235695	12/2004	JP	N/A
2006236994	12/2005	JP	N/A
2006269358	12/2005	JP	N/A
2007227136	12/2006	JP	N/A
2007258160	12/2006	JP	N/A
2008041404	12/2007	JP	N/A
2008048838	12/2007	JP	N/A
2008066094	12/2007	JP	N/A
2008123988	12/2007	JP	N/A
2008140551	12/2007	JP	N/A
2008171593	12/2007	JP	N/A
2008210541	12/2007	JP	N/A
2008226566	12/2007	JP	N/A
2008234879	12/2007	JP	N/A
2008266593	12/2007	JP	N/A
2009064566	12/2008	JP	N/A
2009176552	12/2008	JP	N/A
2009188037	12/2008	JP	N/A
4426721	12/2009	JP	N/A
2010056036	12/2009	JP	N/A
2010123383	12/2009	JP	N/A
2010202987	12/2009	JP	N/A
2011065849	12/2010	JP	N/A
2011233144	12/2010	JP	N/A

2012018773	12/2011	JP	N/A
2012069283	12/2011	JP	N/A
4932263	12/2011	JP	N/A
5183016	12/2012	JP	N/A
2013161684	12/2012	JP	N/A
2013535113	12/2012	JP	N/A
2013535773	12/2012	JP	N/A
2013211185	12/2012	JP	N/A
2014127440	12/2013	JP	N/A
2015018635	12/2014	JP	N/A
2015504234	12/2014	JP	N/A
2015230796	12/2014	JP	N/A
2016110886	12/2015	JP	N/A
2016517161	12/2015	JP	N/A
2016149202	12/2015	JP	N/A
6275313	12/2017	JP	N/A
2021093379	12/2020	JP	N/A
20070069171	12/2006	KR	N/A
20080063793	12/2007	KR	N/A
20090026190	12/2008	KR	N/A
20090052556	12/2008	KR	N/A
20090123894	12/2008	KR	N/A
20100137530	12/2009	KR	N/A
20110079744	12/2010	KR	N/A
20110116489	12/2010	KR	N/A
20120062333	12/2011	KR	N/A
20120110111	12/2011	KR	N/A
20130036043	12/2012	KR	N/A
20130054346	12/2012	KR	N/A
20140024464	12/2013	KR	N/A
20150108040	12/2014	KR	N/A
WO-9102385	12/1990	WO	N/A
WO-9103080	12/1990	WO	N/A
WO-9708763	12/1996	WO	N/A
WO-9931751	12/1998	WO	N/A
WO-9933125	12/1998	WO	N/A
WO-9957770	12/1998	WO	N/A
WO-0076011	12/1999	WO	N/A
WO-0103824	12/2000	WO	N/A
WO-0076011	12/2000	WO	N/A
WO-0139293	12/2000	WO	N/A
WO-0139303	12/2000	WO	N/A
WO-2005011043	12/2004	WO	N/A
WO-2005022674	12/2004	WO	N/A
WO-2006080265	12/2005	WO	N/A
WO-2006123892	12/2005	WO	N/A
WO-2007006011	12/2006	WO	N/A
WO-2007076011	12/2006	WO	N/A
WO-2007095348	12/2006	WO	N/A
WO-2007135790	12/2006	WO	N/A

WO-2007120763	12/2007	WO	N/A
WO-2008087966	12/2007	WO	N/A
WO-2008099468	12/2007	WO	N/A
WO-2008114727	12/2007	WO	N/A
WO-2008143005	12/2007	WO	N/A
WO-2008150070	12/2007	WO	N/A
WO-2009014388	12/2008	WO	N/A
WO-2009026467	12/2008	WO	N/A
WO-2009044741	12/2008	WO	N/A
WO-2009066946	12/2008	WO	N/A
WO-2009066946	12/2008	WO	N/A
WO-2009120812	12/2008	WO	N/A
WO-2010016881	12/2009	WO	N/A
WO-2010103824	12/2009	WO	N/A
WO-2010138176	12/2009	WO	N/A
WO-2010138177	12/2009	WO	N/A
WO-2010138179	12/2009	WO	N/A
WO-2011065849	12/2010	WO	N/A
WO-2012005139	12/2011	WO	N/A
WO-2012011157	12/2011	WO	N/A
WO-2012011944	12/2011	WO	N/A
WO-2012113157	12/2011	WO	N/A
WO-2013139303	12/2012	WO	N/A
WO-2013146126	12/2012	WO	N/A
WO-2014052533	12/2013	WO	N/A
WO-2014119665	12/2013	WO	N/A
WO-2014179355	12/2013	WO	N/A
WO-2015004069	12/2014	WO	N/A
WO-2015074065	12/2014	WO	H01M 10/052
WO-2016168715	12/2015	WO	N/A
WO-2017008081	12/2016	WO	N/A
WO-2018050067	12/2017	WO	N/A
WO-2019074925	12/2018	WO	N/A
WO-2019103011	12/2018	WO	H01G 11/06
WO-2019136467	12/2018	WO	N/A
WO-2021087465	12/2020	WO	N/A
WO-2022040103	12/2021	WO	N/A
WO-2022232625	12/2021	WO	N/A
WO-2024130246	12/2023	WO	N/A

OTHER PUBLICATIONS

Co-pending U.S. Appl. No. 15/262,581, inventor Chiang; Yet-Ming, filed Sep. 12, 2016. cited by applicant

Co-pending U.S. Appl. No. 15/425,368, inventor Slocum; Alexander H., filed Feb. 6, 2017. cited by applicant

Co-pending U.S. Appl. No. 16/139,791, inventors Ota; Naoki et al., filed Sep. 24, 2018. cited by applicant

Co-pending U.S. Appl. No. 16/736,553, inventors Ota; Naoki et al., filed Jan. 7, 2020. cited by

applicant
Co-pending U.S. Appl. No. 18/223,894, inventors Chen; Junzheng et al., filed Jul. 19, 2023. cited by applicant
Co-pending U.S. Appl. No. 18/411,431, inventors Chiang; Yet-Ming et al., filed Jan. 12, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/442,938, inventors Bazzarella; Ricardo et al., filed Feb. 15, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/510,473, inventor Taylor; Tony L., filed Nov. 15, 2023. cited by applicant
Co-pending U.S. Appl. No. 18/526,405, inventor Chiang; Yet-Ming, filed Dec. 1, 2023. cited by applicant
Co-pending U.S. Appl. No. 18/629,597, inventors Ota; Naoki et al., filed Apr. 8, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/658,725, inventor Bazzarella; Ricardo, filed May 8, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/760,721, inventors Lawrence; Ryan Michael et al., filed Jul. 1, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/763,907, inventors Bazzarella; Ricardo et al., filed Jul. 3, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/773,019, inventor Tan; Taison, filed Jul. 15, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/777,389, inventor Chen; Junzheng, filed Jul. 18, 2024. cited by applicant
Co-pending U.S. Appl. No. 18/777,397, inventor Chen; Junzheng, filed Jul. 18, 2024. cited by applicant
Corrected Notice of Allowance for U.S. Appl. No. 18/543,959, mailed Jul. 31, 2024, 2 pages. cited by applicant
Gomez-Martin et al., "Opportunities and Challenges of $\text{Li}_2\text{C}_4\text{O}_4$ as Pre-Lithiation Additive for the Positive Electrode in NMC622||Silicon/Graphite Lithium Ion Cells," *Advanced Science*, Aug. 2022, 9(24):2201742, 15 pages. cited by applicant
Ikezawa A., et al., "Performance of $\text{Li}_4\text{Ti}_5\text{O}_{12}$ -based Reference Electrode for the Electrochemical Analysis of All-solid-state Lithium-ion Batteries," *Electrochemistry Communications*, Jul. 2020, vol. 116: 106743, 5 pages. cited by applicant
International Preliminary Report on Patentability for Application No. PCT/US2020/058564, mailed May 12, 2022, 9 pages. cited by applicant
International Preliminary Report on Patentability for International Application No. PCT/US2022/027104 dated Nov. 9, 2023, 8 pages. cited by applicant
International Search Report and Written Opinion for Application No. PCT/US2022/027104, mailed Dec. 13, 2022, 12 pages. cited by applicant
International Search Report and Written Opinion for International Application No. PCT/US2020/058564, mailed Feb. 1, 2021, 12 pages. cited by applicant
International Search Report and Written Opinion for International Application No. PCT/US2023/084611 dated Apr. 18, 2024, 9 pages. cited by applicant
Lawrence et al., U.S. Appl. No. 63/622,201, titled "Systems and methods of folding electrochemical cell tabs for energy density improvement", filed Jan. 28, 2024, 23 pages. cited by applicant
Liu et al., "Controllable long-term lithium replenishment for enhancing energy density and cycle life of lithium-ion batteries," *Energy & Environmental Science*, 2024, 17(3):1163-1174. cited by applicant
Matsuzaki et al., "Application of Na_2CO_3 as a Sacrificial Electrode Additive in Na-ion Batteries to

Compensate for the Sodium Deficiency in Na₂/3[Fe₁/2Mn₁/2]O₂,” Batteries & Supercaps, May 2024, 7(5):e202400009, 9 pages. cited by applicant

Non-Final Office Action for U.S. Appl. No. 18/543,515 dated Feb. 9, 2024, 14 pages. cited by applicant

Non-Final Office Action for U.S. Appl. No. 18/543,959 dated May 1, 2024, 8 pages. cited by applicant

Notice of Allowance for U.S. Appl. No. 18/543,515 dated Apr. 4, 2024, 10 pages. cited by applicant

Notice of Allowance for U.S. Appl. No. 18/543,959 mailed Jul. 22, 2024, 9 pages. cited by applicant

Notice of Allowance for U.S. Appl. No. 18/650,789 mailed Jul. 19, 2024, 8 pages. cited by applicant

Piana M., et al., “Stability of a Pyrrolidinium-Based Ionic Liquid in Li-0 2 Cells,” Journal of the Electrochemical Society, Jan. 2014, vol. 161(14), pp. A1992-A2001. cited by applicant

Restriction Requirement for U.S. Appl. No. 18/543,959, mailed Apr. 9, 2024, 6 pages. cited by applicant

Holtmann et al., “Boehmite-based ceramic separator for lithium-ion batteries,” Journal of Applied Electrochemistry, Jan. 2016, 46, pp. 69-76, <https://doi.org/10.1007/s10800-015-0895-z>. cited by applicant

Kim et al., “Preparation of a Trilayer Separator and its Application to Lithium-ion Batteries”, Journal of Power Sources, Elsevier SA, CH, Jul. 2, 2010, vol. 195, No. 24, pp. 8302-8305. cited by applicant

Nestler et al., “Separators—Technology Review: Ceramic based Separators for Secondary Batteries,” AIP Conference Proceedings, Jan. 1, 2014, vol. 1597(1), pp. 155-184, New York, US, ISSN: 3084-243X, DOI: 10.1063/1.4878486. cited by applicant

Takemura et al., “A Powder Particle Size Effect on Ceramic Powder Based Separator for Lithium Rechargeable Battery,” Journal of Power Sources, Aug. 2005, vol. 146(102), pp. 779-783. cited by applicant

Uhlhorn, et al., “Synthesis of Ceramic Membranes: Part I Synthesis of non-supported and supported γ-alumina membranes without defects,” Journal of Materials Science, Jan. 1992, 27, pp. 527-537. cited by applicant

Steven et al., U.S. Appl. No. 60/773,487 titled “Methods of preparing separators for electrochemical cells”, filed Feb. 15, 2006, 30 pages. cited by applicant

Zhang et al., “Sulfonated polyimide/AIOOH composite membranes with decreased vanadium permeability and increased stability for vanadium redox flow battery”, Journal of Solid State Electrochemistry, Springer, Berlin, DE, vol. 18, No. 12, Jul. 18, 2014, pp. 3479-3490. cited by applicant

Non-Final Office Action for U.S. Appl. No. 18/777,389 mailed Dec. 3, 2024, 11 pages. cited by applicant

Non-Final Office Action for U.S. Appl. No. 18/777,397 mailed Dec. 5, 2024, 8 pages. cited by applicant

Restriction Requirement for U.S. Appl. No. 17/733,658 mailed Nov. 25, 2024, 7 pages. cited by applicant

Primary Examiner: Essex; Stephan J

Attorney, Agent or Firm: Cooley LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) The present application is a continuation of U.S. patent application Ser. No. 17/733,658, filed Apr. 29, 2022, and entitled “Electrochemical Cells with Multiple Separators, and Methods of Producing the Same,” which claims priority to and benefit of U.S. Provisional Application No. 63/181,721, filed Apr. 29, 2021, and entitled “Electrochemical Cells with Multiple Separators and Methods of Producing the Same,” the entire disclosures of which are incorporated herein by reference.

TECHNICAL FIELD

(1) Embodiments described herein relate to electrochemical cells with multiple separators, and methods of producing the same.

BACKGROUND

(2) Electrolyte is added to electrodes during production of electrochemical cells. Electrolyte is often in the form of an electrolyte solvent with an electrolyte salt dissolved therein. Conventional electrochemical cell production processes include forming solid electrodes, placing them in a container and adding the electrolyte to the container. However, formation of semi-solid electrodes can include adding an electrolyte solution to an active material and a conductive material to form a slurry. During the production process, the slurry can be moved from one location to another, and electrolyte solvent can evaporate from the slurry. This solvent can be costly to replace. Preventing solvent evaporation rather than replacing evaporated solvent can significantly reduce costs associated with production of electrochemical cells.

SUMMARY

(3) Embodiments described herein relate to electrochemical cells with multiple separators, and methods of producing the same. A method of producing an electrochemical cell can include disposing an anode material onto an anode current collector, disposing a first separator on the anode material, disposing a cathode material onto a cathode current collector, disposing a second separator onto the cathode material, and disposing the first separator on the second separator to form the electrochemical cell. The anode material and/or the cathode material can be a semi-solid electrode material including an active material, a conductive material, and a volume of liquid electrolyte. In some embodiments, less than about 10% by volume of the liquid electrolyte evaporates during the forming of the electrochemical cell. In some embodiments, the method can further include wetting the first separator and/or the second separator with an electrolyte solution prior to coupling the first separator to the second separator. In some embodiments, the wetting is via spraying. In some embodiments, less than about 10% by volume of the electrolyte solution evaporates during the forming of the electrochemical cell. In some embodiments, less than about 10% of a total volume of a combination of the electrolyte solution and the liquid electrolyte can evaporate during the forming of the electrochemical cell. In some embodiments, the first separator and/or the second separator can be composed of a material with a porosity of less than about 1%. In some embodiments, the cathode current collector, the cathode material, and the second separator can collectively form a cathode, and the method further comprises conveying the cathode along a cathode conveyor. In some embodiments, the anode current collector, the anode material, and the first separator can collectively form an anode, and the method further comprises conveying the anode along an anode conveyor. In some embodiments, the anode conveyor can be the same conveyor as the cathode conveyor. In some embodiments, the anode conveyor can be a different conveyor from the cathode conveyor.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a block diagram an electrochemical cell with multiple separators, according to an

embodiment.

(2) FIG. 2 is an illustration of an electrochemical cell with multiple separators, according to an embodiment.

(3) FIG. 3 is a block diagram of a method of manufacturing an electrochemical cell with multiple separators, according to an embodiment.

(4) FIGS. 4A-4C show methods of conveyance of electrodes, according to various embodiments.

(5) FIG. 5 is an illustration of an electrochemical cell with multiple separators, according to an embodiment.

(6) FIG. 6 is an illustration of an electrochemical cell with multiple separators, according to an embodiment.

(7) FIG. 7 is an illustration of an electrochemical cell with multiple separators, according to an embodiment.

(8) FIGS. 8A-8B show a comparison between a control electrochemical cell with a single separator and an electrochemical cell with two separators and a layer of hard carbon disposed therebetween.

(9) FIGS. 9A-9B show a comparison between a control electrochemical cell with a single separator and an electrochemical cell with two separators and a layer of hard carbon disposed therebetween.

DETAILED DESCRIPTION

(10) Embodiments described herein relate to multi-separator electrochemical cells and systems, and methods of manufacturing the same. Separators in electrochemical cells physically isolate an anode from a cathode so as to prevent short circuits and maintain a voltage difference between the anode and the cathode. Pores in separators allow passage of electroactive species therethrough. Separators can have an additional benefit of shielding evaporation of electrolyte solution during production.

(11) In some embodiments, electrodes described herein can be semi-solid electrodes. In comparison to conventional electrodes, semi-solid electrodes can be made (i) thicker (e.g., greater than about 250 μm -up to about 2,000 μm or even greater) due to the reduced tortuosity and higher electronic conductivity of semi-solid electrodes, (ii) with higher loadings of active materials, (iii) with a simplified manufacturing process utilizing less equipment, and (iv) can be operated between a wide range of C-rates while maintaining a substantial portion of their theoretical charge capacity. These relatively thick semi-solid electrodes decrease the volume, mass and cost contributions of inactive components with respect to active components, thereby enhancing the commercial appeal of batteries made with the semi-solid electrodes. In some embodiments, the semi-solid electrodes described herein, are binderless and/or do not use binders that are used in conventional battery manufacturing. Instead, the volume of the electrode normally occupied by binders in conventional electrodes, is now occupied, by: 1) electrolyte, which has the effect of decreasing tortuosity and increasing the total salt available for ion diffusion, thereby countering the salt depletion effects typical of thick conventional electrodes when used at high rate, 2) active material, which has the effect of increasing the charge capacity of the battery, or 3) conductive additive, which has the effect of increasing the electronic conductivity of the electrode, thereby countering the high internal impedance of thick conventional electrodes. The reduced tortuosity and a higher electronic conductivity of the semi-solid electrodes described herein, results in superior rate capability and charge capacity of electrochemical cells formed from the semi-solid electrodes.

(12) Since the semi-solid electrodes described herein can be made substantially thicker than conventional electrodes, the ratio of active materials (i.e., the semi-solid cathode and/or anode) to inactive materials (i.e., the current collector and separator) can be much higher in a battery formed from electrochemical cell stacks that include semi-solid electrodes relative to a similar battery formed from electrochemical cell stacks that include conventional electrodes. This substantially increases the overall charge capacity and energy density of a battery that includes the semi-solid electrodes described herein. The use of semi-solid, binderless electrodes can also be beneficial in the incorporation of an overcharge protection mechanism, as generated gas can migrate to the electrode/current collector interface without binder particles inhibiting the movement of the gas

within the electrode.

(13) In some embodiments, the electrode materials described herein can be a flowable semi-solid or condensed liquid composition. A flowable semi-solid electrode can include a suspension of an electrochemically active material (anodic or cathodic particles or particulates), and optionally an electronically conductive material (e.g., carbon) in a non-aqueous liquid electrolyte. Said another way, the active electrode particles and conductive particles are co-suspended in a liquid electrolyte to produce a semi-solid electrode. Examples of electrochemical cells that include a semi-solid and/or binderless electrode material are described in U.S. Pat. No. 8,993,159 entitled, “Semi-solid Electrodes Having High Rate Capability,” filed Apr. 29, 2013 (“the '159 patent”), the disclosure of which is incorporated herein by reference in its entirety.

(14) In some embodiments, the electrode materials described herein can be a flowable semi-solid or condensed liquid composition. In some embodiments, a flowable semi-solid electrode can include a suspension of an electrochemically active material (anodic or cathodic particles or particulates), and optionally an electronically conductive material (e.g., carbon) in a non-aqueous liquid electrolyte. In some embodiments, the active electrode particles and conductive particles can be co-suspended in an electrolyte to produce a semi-solid electrode. In some embodiments, electrode materials described herein can include conventional electrode materials (e.g., including lithium metal).

(15) Semi-solid electrodes have a liquid electrolyte integrated therein during a longer portion of the manufacturing process than conventional electrodes, which add electrolyte solution after the electrodes are fully formed. In other words, liquid electrolyte is added to conductive materials and/or active materials to form a semi-solid electrode material. While the semi-solid electrode material is undergoing further processing, liquid electrolyte solvent can evaporate from the semi-solid electrode material. This evaporation can raise the molarity of electrolyte salt in the electrolyte solution, potentially causing salt buildup. Built-up salt can prevent passage of electroactive species through the semi-solid electrode material. In other words, movement of electroactive species through pores of the semi-solid electrode material can be more difficult when salt ions build up and block flow paths. Additionally, evaporation of electrolyte solution can make the semi-solid electrode material less flowable and/or less malleable. Liquid flow paths within the semi-solid electrode material can dry out, increasing tortuosity of the movements of electroactive species.

(16) While adding electrolyte solvent during production can address some of these problems, make-up electrolyte solvent can add significant cost to the production process. Coupling separators to the anode and/or the cathode during production of the electrochemical cell can aid in reducing evaporation of electrolyte solvent during production. In some embodiments, separators described herein can have geometries and general properties the same or substantially similar to those described in PCT Application US2020/058564 entitled “Electrochemical Cells with Separator Seals, and Methods of Manufacturing the Same,” filed Nov. 2, 2020 (“the '564 application”), the disclosure of which is hereby incorporated by reference in its entirety.

(17) FIG. 1 is a block diagram of an electrochemical cell **100** with multiple separators, according to an embodiment. As shown, the electrochemical cell **100** includes an anode material **110** disposed on an anode current collector **120** and a cathode material **130** disposed on a cathode current collector **140**, with a first separator **150a** and a second separator **150b** (collectively referred to as “separators **150**”) disposed therebetween. In some embodiments, the anode material **110** and/or the cathode material **130** can include a semi-solid electrode material. In some embodiments, the anode material **110** and/or the cathode material **130** can include any of the properties of the semi-solid electrodes described in the '159 patent.

(18) In some embodiments, the anode material **110** and/or the cathode material **130** can include at least about 0.1%, at least about 0.2%, at least about 0.3%, at least about 0.4%, at least about 0.5%, at least about 0.6%, at least about 0.7%, at least about 0.8%, at least about 0.9%, at least about 1%, at least about 2%, at least about 3%, at least about 4%, at least about 5%, at least about 6%, at least

about 7%, at least about 8%, at least about 9%, at least about 10%, at least about 11%, at least about 12%, at least about 13%, at least about 14%, at least about 15%, at least about 16%, at least about 17%, at least about 18%, at least about 19%, at least about 20%, at least about 21%, at least about 22%, at least about 23%, or at least about 24% by volume of liquid electrolyte solution. In some embodiments, the anode material **110** and/or the cathode material **130** can include no more than about 25%, no more than about 24%, no more than about 23%, no more than about 22%, no more than about 21%, no more than about 20%, no more than about 19%, no more than about 18%, no more than about 17%, no more than about 16%, no more than about 15%, no more than about 14%, no more than about 13%, no more than about 12%, no more than about 11%, no more than about 10%, no more than about 9%, no more than about 8%, no more than about 7%, no more than about 6%, no more than about 5%, no more than about 4%, no more than about 3%, no more than about 2%, no more than about 1%, no more than about 0.9%, no more than about 0.8%, no more than about 0.7%, no more than about 0.6%, no more than about 0.5%, no more than about 0.4%, no more than about 0.3%, or no more than about 0.2% by volume of liquid electrolyte solution.

(19) Combinations of the above-referenced volumetric percentages of liquid electrolyte solution in the anode material **110** and/or the cathode material **130** are also possible (e.g., at least about 0.1% and no more than about 25% or at least about 5% and no more than about 10%), inclusive of all values and ranges therebetween. In some embodiments, the anode material **110** and/or the cathode material **130** can include about 0.1%, about 0.2%, about 0.3%, about 0.4%, about 0.5%, about 0.6%, about 0.7%, about 0.8%, about 0.9%, about 1%, about 2%, about 3%, about 4%, about 5%, about 6%, about 7%, about 8%, about 9%, about 10%, about 11%, about 12%, about 13%, about 14%, about 15%, about 16%, about 17%, about 18%, about 19%, about 20%, about 21%, about 22%, about 23%, about 24%, or about 25% by volume of liquid electrolyte solution.

(20) In some embodiments, the anode current collector **120** and/or the cathode current collector **140** can be composed of copper, aluminum, titanium, or other metals that do not form alloys or intermetallic compounds with lithium, carbon, and/or coatings comprising such materials disposed on another conductor. In some embodiments, the anode current collector **120** and/or the cathode current collector **140** can have a thickness of at least about 1 μm , at least about 5 μm , at least about 10 μm , at least about 15 μm , at least about 20 μm , at least about 25 μm , at least about 30 μm , at least about 35 μm , at least about 40 μm , or at least about 45 μm . In some embodiments, the anode current collector **120** and/or the cathode current collector **140** can have a thickness of no more than about 50 μm , no more than about 45 μm , no more than about 40 μm , no more than about 35 μm , no more than about 30 μm , no more than about 25 μm , no more than about 20 μm , no more than about 15 μm , no more than about 10 μm , or no more than about 5 μm . Combinations of the above-referenced thicknesses of the anode current collector **120** and/or the cathode current collector **140** are also possible (e.g., at least about 1 μm and no more than about 50 μm or at least about 10 μm and no more than about 30 μm), inclusive of all values and ranges therebetween. In some embodiments, the anode current collector **120** and/or the cathode current collector **140** can have a thickness of about 1 μm , about 5 μm , about 10 μm , about 15 μm , about 20 μm , about 25 μm , about 30 μm , about 35 μm , about 40 μm , about 45 μm , or about 50 μm .

(21) In some embodiments, the anode material **110** can include a first electrolyte and the cathode material **130** can include a second electrolyte. In other words, and the anode material **110** can include an anolyte and the cathode material **130** can include a catholyte. In some embodiments, the electrochemical cell **100** can include an anolyte disposed on the anode side of the separators **150**. In some embodiments, the electrochemical cell **100** can include a catholyte disposed on the cathode side of the separators **150**. In some embodiments, the electrochemical cell **100** can include a selectively permeable membrane. In some embodiments, the selectively permeable membrane can be disposed between the first separator **150a** and the second separator **150b**. Electrochemical cells with anolytes, catholytes, and/or selectively permeable membranes are described in U.S. Pat. No. 10,734,672 ("the '672 patent"), filed Jan. 8, 2019, and titled, "Electrochemical Cells Including

Selectively Permeable Membranes, Systems and Methods of Manufacturing the Same,” the disclosure of which is hereby incorporated by reference in its entirety.

(22) As shown, the first separator **150a** is disposed on the anode material **110** while the second separator **150b** is disposed on the cathode material **130**. In some embodiments, the separators **150** can be disposed on their respective electrodes during production of the electrochemical cell **100**. In some embodiments, the first separator **150a** and/or the second separator **150b** can be composed of polyethylene, polypropylene, high density polyethylene, polyethylene terephthalate, polystyrene, a thermosetting polymer, hard carbon, a thermosetting resin, a polyimide, a ceramic coated separator, an inorganic separator, cellulose, glass fiber, a polyethylenoxide (PEO) polymer in which a lithium salt is complexed to provide lithium conductivity, Nasion™ membranes which are proton conductors, or any other suitable separator material, or combinations thereof. In some embodiments, the first separator **150a** and/or the second separator **150b** can be composed of any of the separator materials described in the '564 application. In some embodiments, the first separator **150a** can be composed of the same material as the second separator **150b**. In some embodiments, the first separator **150a** can be composed of a different material from the second separator **150b**. In some embodiments, the first separator **150a** and/or the second separator **150b** can be absent of any framing members described in the '564 application.

(23) In some embodiments, the first separator **150a** and/or the second separator **150b** can have a porosity of at least about 5%, at least about 10%, at least about 15%, at least about 20%, at least about 25%, at least about 30%, at least about 35%, at least about 40%, at least about 45%, at least about 50%, at least about 55%, at least about 60%, at least about 65%, at least about 70%, at least about 75%, at least about 80%, or at least about 85%. In some embodiments, the first separator **150a** and/or the second separator **150b** can have a porosity of no more than about 90%, no more than about 85%, no more than about 80%, no more than about 75%, no more than about 70%, no more than about 65%, no more than about 60%, no more than about 55%, no more than about 50%, no more than about 45%, no more than about 40%, no more than about 35%, no more than about 30%, no more than about 25%, no more than about 20%, no more than about 15%, or no more than about 10%.

(24) Combinations of the above-referenced porosity percentages of the first separator **150a** and/or the second separator **150b** are also possible (e.g., at least about 5% and no more than about 90% or at least about 20% and no more than about 40%), inclusive of all values and ranges therebetween. In some embodiments, the first separator **150a** and/or the second separator **150b** can have a porosity of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, about 70%, about 75%, about 80%, about 85%, or about 90%.

(25) In some embodiments, the first separator **150a** can have a different porosity from the second separator **150b**. In some embodiments, the porosities of the first separator **150a** and the second separator **150b** can be selected based on the difference between the anolyte and the catholyte. For example, if the catholyte has a higher vapor pressure and faster evaporation properties than the anolyte, then the second separator **150b** can have a lower porosity than the first separator **150a**. The lower porosity of the second separator **150b** can at least partially prevent the catholyte from evaporating during production.

(26) In some embodiments, the first separator **150a** can be composed of a different material from the second separator **150b**. In some embodiments, the materials of the first separator **150a** and the second separator **150b** can be selected to facilitate wettability of the first separator **150a** with the anolyte and the second separator **150b** with the catholyte **150**. For example, an ethylene carbonate/propylene carbonate-based catholyte can wet a polyethylene separator better than a polyimide separator, based on the molecular properties of the materials. An ethylene carbonate/dimethyl carbonate-based anolyte can wet a polyimide separator better than a polyethylene separator. A full wetting of the first separator **150a** and the second separator **150b** can give way to better

transport of electroactive species via the separators **150**. This transport can be facilitated particularly well when the first separator **150a** physically contacts the second separator **150b**. (27) In some embodiments, the first separator **150a** and/or the second separator **150b** can be absent of separator seals (e.g., separator seals described in the '564 application). As shown, the electrochemical cell **100** includes two separators **150**. In some embodiments, the electrochemical cell **100** can include 3, 4, 5, 6, 7, 8, 9, 10, or more than about 10 separators **150**. In some embodiments, a layer of liquid electrolyte (not shown) can be disposed between the first separator **150a** and the second separator **150b**. A layer of liquid electrolyte can promote better adhesion between the separators **150**.

(28) In some embodiments, the first separator **150a** and/or the second separator **150b** can have a thickness of at least about 1 μm , at least about 2 μm , at least about 3 μm , at least about 4 μm , at least about 5 μm , at least about 6 μm , at least about 7 μm , at least about 8 μm , at least about 9 μm , at least about 10 μm , at least about 20 μm , at least about 30 μm , at least about 40 μm , at least about 50 μm , at least about 60 μm , at least about 70 μm , at least about 80 μm , at least about 90 μm , at least about 100 μm , at least about 110 μm , at least about 120 μm , at least about 130 μm , at least about 140 μm , at least about 150 μm , at least about 160 μm , at least about 170 μm , at least about 180 μm , or at least about 190 μm . In some embodiments, the first separator **150a** and/or the second separator **150b** can have a thickness of no more than about 200 μm , no more than about 190 μm , no more than about 180 μm , no more than about 170 μm , no more than about 160 μm , no more than about 150 μm , no more than about 140 μm , no more than about 130 μm , no more than about 120 μm , no more than about 110 μm , no more than about 100 μm , no more than about 90 μm , no more than about 80 μm , no more than about 70 μm , no more than about 60 μm , no more than about 50 μm , no more than about 40 μm , no more than about 30 μm , no more than about 20 μm , no more than about 10 μm , no more than about 9 μm , no more than about 8 μm , no more than about 7 μm , no more than about 6 μm , no more than about 5 μm , no more than about 4 μm , no more than about 3 μm , or no more than about 2 μm . Combinations of the above-referenced thicknesses of the first separator **150a** and/or the second separator **150b** are also possible (e.g., at least about 1 μm and no more than about 200 μm or at least about 50 μm and no more than about 100 μm), inclusive of all values and ranges therebetween. In some embodiments, the first separator **150a** and/or the second separator **150b** can have a thickness of about 1 μm , about 2 μm , about 3 μm , about 4 μm , about 5 μm , about 6 μm , about 7 μm , about 8 μm , about 9 μm , about 10 μm , about 20 μm , about 30 μm , about 40 μm , about 50 μm , about 60 μm , about 70 μm , about 80 μm , about 90 μm , about 100 μm , about 110 μm , about 120 μm , about 130 μm , about 140 μm , about 150 μm , about 160 μm , about 170 μm , about 180 μm , about 190 μm , or about 200 μm . In some embodiments, the first separator **150a** can have a thickness the same or substantially similar to the thickness of the second separator **150b**. In some embodiments, the first separator **150a** can have a thickness greater or less than a thickness of the second separator **150b**.

(29) In some embodiments, the first separator **150a** can be coupled to the second separator **150b**. In some embodiments, the first separator **150a** and/or the second separator **150b** can be wetted so as to promote clinging between first separator **150a** and the second separator **150b**. In other words, the first separator **150a** can be held to the second separator **150b** via surface tension and/or capillary forces.

(30) In some embodiments, the anode material **110**, the anode current collector **120**, and the first separator **150a** can be packaged in a first container, while the cathode material **130**, the cathode current collector **140** and the second separator **150b** can be packaged in a second container prior to assembly. In other words, the electrochemical cell **100** can be assembled via an anode kit (including the anode material **110**, the anode current collector **120**, and the first separator **150a**) and a cathode kit (including the cathode material **130**, the cathode current collector **140**, and the second separator **150b**). The anode material **110**, the anode current collector **120**, and the first separator **150a** can be removed from the first container and the cathode material **130**, the cathode current

collector **140**, and the second separator **150b** can be removed from the second container. The first separator **150a** can then be disposed on the second separator **150b** to form the electrochemical cell **100**.

(31) FIG. 2 shows an illustration of an electrochemical cell **200**, according to an embodiment. As shown, the electrochemical cell **200** includes an anode material **210** disposed on an anode current collector **220**, a cathode material **230** disposed on a cathode current collector **240**, a first separator **250a** disposed on the anode material **210**, a second separator **250b** disposed on the cathode material **230**, and an interlayer **260** disposed between the first separator **250a** and the second separator **250b**. In some embodiments, the anode material **210**, the anode current collector **220**, the cathode material **230**, the cathode current collector **240**, the first separator **250a**, and the second separator **250b** can be the same or substantially similar to the anode material **110**, the anode current collector **120**, the cathode material **130**, the cathode current collector **140**, the first separator **150a**, and the second separator **150b**, as described above with reference to FIG. 1. Thus, certain aspects of the anode material **210**, the anode current collector **220**, the cathode material **230**, the cathode current collector **240**, the first separator **250a**, and the second separator **250b** are not described in greater detail herein.

(32) In some embodiments, the interlayer **260** can include an electrolyte layer. In some embodiments, the electrolyte layer can include a liquid electrolyte. In some embodiments, the electrolyte layer can include a solid-state electrolyte, for example, to prevent dendrite growth. In some embodiments, the electrolyte layer can include polyacrylonitrile (PAN). In some embodiments, the electrolyte layer can partially or fully saturate the first separator **250a** and/or the second separator **250b** (collectively referred to as the separators **250**). In some embodiments, the electrolyte layer can aid in bonding the first separator **250a** to the second separator **250b**. In some embodiments, the electrolyte layer can create a surface tension to bond the first separator **250a** to the second separator **250b**. In some embodiments, the electrolyte layer can facilitate movement of electroactive species between the anode material **210** and the cathode material **230**.

(33) In some embodiments, the interlayer **260** can have a thickness of at least about 500 nm, at least about 1 μm , at least about 2 μm , at least about 3 μm , at least about 4 μm , at least about 5 μm , at least about 6 μm , at least about 7 μm , at least about 8 μm , at least about 9 μm , at least about 10 μm , at least about 20 μm , at least about 30 μm , at least about 40 μm , at least about 50 μm , at least about 60 μm , at least about 70 μm , at least about 80 μm , or at least about 90 μm . In some embodiments, the interlayer **260** can have a thickness of no more than about 100 μm , no more than about 90 μm , no more than about 80 μm , no more than about 70 μm , no more than about 60 μm , no more than about 50 μm , no more than about 40 μm , no more than about 30 μm , no more than about 20 μm , no more than about 10 μm , no more than about 9 μm , no more than about 8 μm , no more than about 7 μm , no more than about 6 μm , no more than about 5 μm , no more than about 4 μm , no more than about 3 μm , no more than about 2 μm , or no more than about 1 μm . Combinations of the above-referenced thicknesses of the interlayer **260** are also possible (e.g., at least about 500 nm and no more than about 100 μm or at least about 2 μm and no more than about 30 μm), inclusive of all values and ranges therebetween. In some embodiments, the interlayer **260** can have a thickness of about 500 nm, about 1 μm , about 2 μm , about 3 μm , about 4 μm , about 5 μm , about 6 μm , about 7 μm , about 8 μm , about 9 μm , about 10 μm , about 20 μm , about 30 μm , about 40 μm , about 50 μm , about 60 μm , about 70 μm , about 80 μm , about 90 μm , or about 100 μm .

(34) In some embodiments, the interlayer **260** can include a semi-solid electrode layer disposed between the first separator **250a** and the second separator **250b**. In some embodiments, the layer of semi-solid electrode material can be included in addition to the electrolyte layer. In some embodiments, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can include a material that reacts with metallic lithium. In some embodiments, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can include hard carbon, graphite, or any other suitable electrode material or combinations thereof. In

some embodiments, if the anode material **210** begins to form dendrites that penetrate the first separator **250a**, the dendritic material can react with the semi-solid electrode layer between the first separator **250a** and the second separator **250b**, such that the dendrites dissipate, thus preventing a short circuit. In some embodiments, the interlayer **260** may include a single layer. In some embodiments, the interlayer **260** may include a bilayer structure, for example, include a first layer including a semi-solid electrode layer (e.g., a binder-free carbon slurry), and a second layer including a solid state electrolyte (e.g., LLZO, LLTO, LATP, sulfides, polymer gel electrolytes, etc.).

(35) In some embodiments, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can aid in transporting electroactive species across the separators **250**. The semi-solid electrode layer between the first separator **250a** and the second separator **250b** can provide reduced tortuosity and better lithium ion diffusion compared to conventional electrode materials. The composition of the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can be fine-tuned to facilitate ion movement therethrough.

(36) In some embodiments, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can have catalytic effects to remove, dissolve, and/or corrode contaminating metal powders (e.g., iron, chromium, nickel, aluminum, copper). In such cases, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can serve as a metal contamination removing buffer layer. In some embodiments, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can include a non-lithium ion semi-solid slurry with an aligned pore structure, a high surface area, and/or a diffusive structure combined with an electrolyte. Such materials can include metal-organic frameworks (MOFs), carbon black, an anode aluminum oxide (AAO) template, and/or silica. In such cases, the semi-solid electrode layer between the first separator **250a** and the second separator **250b** can serve as an electrolyte reservoir and/or an embedding base for a dendrite-removing catalyst. Such materials can also improve current distributions in the electrochemical cell **200**. In some embodiments, the dendrite-removing catalyst can include a metal base and/or a polymer base for the facilitation of redox reactions. In some embodiments, the dendrite-removing catalyst can include fluorine, sulfide, or any other suitable catalyst or combinations thereof. In some embodiments, the catalyst can include a base polymer coating mix or a carbon mix.

(37) In some embodiments, the interlayer **260** can include a conventional (i.e., solid) electrode layer can be disposed between the first separator **250a** and the second separator **250b**. In some embodiments, the conventional electrode layer between the first separator **250a** and the second separator **250b** can include a binder (e.g., a solid binder or a gel binder).

(38) In some embodiments, the interlayer **260** can include a polyolefin, a solid-state electrolyte sheet, and/or a polymer electrolyte sheet. In some embodiments, the interlayer **260** can include polyacrylonitrile (PAN), poly(vinylidene fluoride-co-hexafluoropropylene) (PVDF-HFP), poly(methyl methacrylate) (PMMA), polyacrylic acid (PAA), polyethylene oxide (PEO), or any combination thereof.

(39) In some embodiments, the interlayer **260** can include a cathode. In some embodiments, the cathode in the interlayer **260** can include lithium titanate (LTO), hard carbon (HC), and/or any other material with a high impedance connection. In some embodiments, the LTO can include an electron-conductive LTO, such as $\text{Li}_{0.4+x}\text{Ti}_{0.5}\text{O}_{1.2}$ and/or $\text{Li}_{0.4}\text{Ti}_{0.5}\text{O}_{1.2-x}$. In some embodiments, the interlayer **260** can include lithium iron phosphate (LFP) with a high impedance connection. The LFP can be considered a safe chemistry for the monitoring of dendrite formation. If a dendrite forms in either of the electrodes and penetrates into the interlayer **260**, the dendrite would be consumed. Also, voltage can be monitored between the interlayer **260** and the anode current collector **220**, as shown. In some embodiments, voltage can be monitored between the interlayer **260** and the cathode current collector **240**. This voltage monitoring can detect if a dendrite has reached the interlayer **260**.

(40) Measuring voltage between the interlayer **260** and the anode current collector **220** and/or the cathode current collector **240** can be a more efficient method of detecting defects in the electrochemical cell **200** than measuring across the entire electrochemical cell **200** (i.e., between the anode current collector **220** and the cathode current collector **240**), particularly in modules with multiple cells. In some embodiments, multiple electrochemical cells can be connected in parallel and/or series to produce a cell module. For example, if a cell has a capacity of 3 Ah, 50 such cells can be connected in parallel to produce a capacity of 150 Ah. In some embodiments, the module can include about 1, about 2, about 3, about 4, about 5, about 6, about 7, about 8, about 9, about 10, about 11, about 12, about 13, about 14, about 15, about 16, about 17, about 18, about 19, about 20, about 25, about 30, about 35, about 40, about 45, about 50, about 55, about 60, about 65, about 70, about 75, about 80, about 85, about 90, about 95, or about 100 electrochemical cells connected in series and/or parallel, inclusive of all values and ranges therebetween. In monitoring the voltage across the interlayer **260** and the anode current collector **220** and/or the cathode current collector **240**, the interlayer **260** can serve as a reference electrode.

(41) In some embodiments, individual electrochemical cell in a module can have a capacity of about 0.5 Ah, about 1 Ah, about 2 Ah, about 3 Ah, about 4 Ah, about 5 Ah, about 6 Ah, about 7 Ah, about 8 Ah, about 9 Ah, or about 10 Ah, inclusive of all values and ranges therebetween. In some embodiments, modules described herein can have a capacity of about 10 Ah, about 20 Ah, about 30 Ah, about 40 Ah, about 50 Ah, about 60 Ah, about 70 Ah, about 80 Ah, about 90 Ah, about 100 Ah, about 110 Ah, about 120 Ah, about 130 Ah, about 140 Ah, about 150 Ah, about 160 Ah, about 170 Ah, about 180 Ah, about 190 Ah, about 200 Ah, about 210 Ah, about 220 Ah, about 230 Ah, about 240 Ah, about 250 Ah, about 260 Ah, about 270 Ah, about 280 Ah, about 290 Ah, or about 300 Ah, inclusive of all values and ranges therebetween.

(42) In existing battery management systems (BMS) and cell modules, the ability to diagnose the health of each electrochemical cell is limited. To monitor the health of each cell, local voltage and/or current measurements are used to discern small changes in cell voltages. Voltage measurements across individual cells offer little direct correlation to the individual cell health. The addition of differential current measurement in the modules adversely affects the total system complexity and the cost of the measurement systems. Conversely, if the voltage between the interlayer **260** and a current collector is measured for each parallel electrochemical cell, the relative difference of that voltage is a direct measure of the relative health (i.e., impedance) of the anode material **210** and/or the cathode material **230** and relative impedance within the electrochemical cell **200** itself. In such an arrangement, it is possible to determine (by direct measurement) if the electrochemical cell **200** is behaving normally relative to other electrochemical cells in a parallel string or pack system. Through mass data collection, trend data from a large collection of electrochemical cells can be used to coordinate the analysis of a group or lot, or individual cell serial numbers relative to the larger cell population.

(43) For extremely large format cells, the added complexity to measure an additional 2-3 differential voltages is lower than the added complexity of adding equivalent high gain current measurement channels, or to add hall effect type sensors, for example. In this way, individual cell health of a parallel cell grouping can be directly measured. Additional diagnostics to remaining cells connected in series can be evaluated based on state-of-charge (SOC) and state-of-health (SOH) algorithms. This allows for early notification of system failures long before faults would normally be detected. This precision can also allow for a prediction of a date of failure and advanced planning. For example, materials can be positioned properly in an electrochemical cell module in anticipation of a failure. Additionally, supply chain issues can be considered before an original equipment manufacturer (OEM) fleet or an individual consumer is notified of a fault. After the voltage measurement between the interlayer **260** and the anode current collector **220** and/or the cathode current collector **240** detects a soft short-circuit, an external short of the cell module can be triggered to discharge.

(44) In some embodiments, the interlayer **260** can prevent dangerous short circuit events from dendrite growth via metal contamination (e.g., iron contamination, zinc contamination, copper contamination) and shuttling by a buffer layer. In such a case, an iron dendrite can grow and touch hard carbon, graphite, and/or other carbon-containing materials in the interlayer **260**, with the interlayer **260** having a cathode potential. Once the iron dendrite touches the hard carbon, graphite, and/or the other carbon-containing materials in the interlayer **260**, the iron dissolves under the cathode potential, but the high current moving through the electrochemical cell **200** persists via a connection through a diode or high resistance. When metal contamination is used to prevent dangerous short circuit events, voltage can be monitored between the interlayer **260** and the anode current collector **220** and/or the cathode current collector **240** (or between the interlayer **260** and the anode material **210** and/or the cathode material **230**). In some embodiments, additional safety actions can be triggered by a BMS if a significant voltage drop (e.g., at least about 0.5 V, at least about 1 V, at least about 1.5 V, at least about 2 V, at least about 2.5 V, at least about 3 V, at least about 3.5 V, at least about 4 V, at least about 4.5 V, at least about 5 V, inclusive of all values and ranges therebetween) is detected. In some embodiments, the interlayer **260** may include a tab to enable coupling with an electrical connection or sensing system external to the electrochemical cell **200**. In some embodiments, multiple electrochemical cells can be connected in parallel with a tab connected to the interlayer **260**. A diode or high resistance resistor can be connected to many cathodes (e.g., many tabs connected to cathode current collectors **240**) and many interlayers (e.g., many tabs connected to interlayers **260**).

(45) In some embodiments, the interlayer **260** can prevent dangerous short circuit events from lithium dendrites via lithium intercalation. For example, lithium dendrites can grow and penetrate the first separator **250a** or the second separator **250b** and contact hard carbon, graphite, and/or a carbon-containing material in the interlayer **260**. Once the lithium dendrite contacts the hard carbon, graphite, and/or the carbon-containing material in the interlayer **260**, the lithium intercalates into the carbon, graphite, and/or the carbon-containing material. While hard carbon, graphite, and/or any carbon-containing material can facilitate lithium intercalation, any material that reacts with lithium can achieve this lithium intercalation function. In some embodiments, the interlayer **260** can include silicon, aluminum, silver, tungsten, tin, or any combination thereof.

(46) FIG. 3 shows a block diagram of a method **10** of forming an electrochemical cell, according to an embodiment. As shown, the method **10** includes disposing an anode material onto an anode current collector at step **11** and disposing a first separator onto the anode material at step **12**. The method **10** optionally includes conveying the anode current collector, the anode material, and the first separator (collectively referred to as “the anode”) in step **13**. The method **10** further includes disposing a cathode material onto a cathode current collector at step **14** and disposing a second separator onto the cathode material at step **15**. The method **10** optionally includes conveying the cathode current collector, the cathode material, and the second separator (collectively referred to as “the cathode”) at step **16** and wetting the first separator and/or the second separator at step **17**. The method **10** includes coupling the first separator to the second separator at step **18** to form the electrochemical cell.

(47) Step **11** includes disposing the anode material onto the anode current collector. The anode material and the anode current collector can have any of the properties of the anode material **110** and the anode current collector **120** (e.g., thickness, composition) as described above with reference to FIG. 1. In some embodiments, the anode material can be extruded (e.g., via a twin-screw extruder) onto the anode current collector. In some embodiments, the anode material can be dispensed via a nozzle. In some embodiments, the dispensation of the anode material can be via any of the methods described in U.S. provisional application 63/115,293 (hereinafter “the '293 application”), entitled, “Methods of Continuous and Semi-Continuous Production of Electrochemical Cells,” filed Nov. 18, 2020, the entirety of which is incorporated herein by reference. In some embodiments, the dispensation of the anode material can be via any of the

methods described in U.S. patent publication no. 2020/0014025 (hereinafter “the '025 publication”), entitled “Continuous and Semi-Continuous Methods of Semi-Solid Electrode and Battery Manufacturing,” filed Jul. 9, 2019, the entirety of which is hereby incorporated by reference.

(48) Step 12 includes disposing the first separator onto the anode material. In some embodiments, the first separator can be pre-soaked or pre-coated with electrolyte solution prior to the disposing. In some embodiments, the first separator can be placed onto the anode material by a machine. In some embodiments, the first separator can be placed onto the anode material via one or more rollers, conveying separator material. In some embodiments, the separator can be placed onto the anode material via any of the methods described in the '293 application and/or the '025 publication.

(49) Step 13 optionally includes conveying the anode. In some embodiments, the conveying can be on a conveyance device, such as a conveyor belt. In some embodiments, the conveying can be through a tunnel to limit evaporation of electrolyte solution from the anode. In some embodiments, the anode can be on the conveyance device for at least about 1 second, at least about 5 seconds, at least about 10 seconds, at least about 20 seconds, at least about 30 seconds, at least about 40 seconds, at least about 50 seconds, at least about 1 minute, at least about 5 minutes, at least about 10 minutes, at least about 20 minutes, at least about 30 minutes, at least about 40 minutes, at least about 50 minutes, at least about 1 hour, at least about 2 hours, at least about 3 hours, at least about 4 hours, at least about 5 hours, at least about 10 hours, at least about 15 hours, or at least about 20 hours. In some embodiments, the anode can be on the conveyance device for no more than about 1 day, no more than about 20 hours, no more than about 15 hours, no more than about 10 hours, no more than about 5 hours, no more than about 4 hours, no more than about 3 hours, no more than about 2 hours, no more than about 1 hour, no more than about 50 minutes, no more than about 40 minutes, no more than about 30 minutes, no more than about 20 minutes, no more than about 10 minutes, no more than about 5 minutes, no more than about 4 minutes, no more than about 3 minutes, no more than about 2 minutes, no more than about 1 minute, no more than about 50 seconds, no more than about 40 seconds, no more than about 30 seconds, no more than about 20 seconds, no more than about 10 seconds, or no more than about 5 seconds.

(50) Combinations of the above-referenced time periods the anode remains on the conveyance device are also possible (e.g., at least about 1 second and no more than about 1 day or at least about 5 minutes and no more than about 2 hours), inclusive of all values and ranges therebetween. In some embodiments, the anode can be on the conveyance device for about 1 second, about 5 seconds, about 10 seconds, about 20 seconds, about 30 seconds, about 40 seconds, about 50 seconds, about 1 minute, about 5 minutes, about 10 minutes, about 20 minutes, about 30 minutes, about 40 minutes, about 50 minutes, about 1 hour, about 2 hours, about 3 hours, about 4 hours, about 5 hours, about 10 hours, about 15 hours, about 20 hours, or about 1 day.

(51) In some embodiments, the anode can be conveyed a distance of at least about 1 cm, at least about 2 cm, at least about 3 cm, at least about 4 cm, at least about 5 cm, at least about 10 cm, at least about 20 cm, at least about 30 cm, at least about 40 cm, at least about 50 cm, at least about 60 cm, at least about 70 cm, at least about 80 cm, at least about 90 cm, at least about 1 m, at least about 2 m, at least about 3 m, at least about 4 m, at least about 5 m, at least about 6 m, at least about 7 m, at least about 8 m, at least about 9 m, at least about 10 m, at least about 20 m, at least about 30 m, at least about 40 m, at least about 50 m, at least about 60 m, at least about 70 m, at least about 80 m, or at least about 90 m. In some embodiments, the anode can be conveyed a distance of no more than about 100 m, no more than about 90 m, no more than about 80 m, no more than about 70 m, no more than about 60 m, no more than about 50 m, no more than about 40 m, no more than about 30 m, no more than about 20 m, no more than about 10 m, no more than about 9 m, no more than about 8 m, no more than about 7 m, no more than about 6 m, no more than about 5 m, no more than about 4 m, no more than about 3 m, no more than about 2 m, no more than about 1 m, no more than about 90 cm, no more than about 80 cm, no more than about 70 cm, no more than about 60 cm, no more than about 50 cm, no more than about 40 cm, no more than about

30 cm, no more than about 20 cm, no more than about 10 cm, no more than about 9 cm, no more than about 8 cm, no more than about 7 cm, no more than about 6 cm, no more than about 5 cm, no more than about 4 cm, no more than about 3 cm, or no more than about 2 cm. Combinations of the above-referenced conveyance distances are also possible (e.g., at least about 1 cm and no more than about 100 m or at least about 50 cm and no more than about 20 m), inclusive of all values and ranges therebetween. In some embodiments, the anode can be conveyed about 1 cm, about 2 cm, about 3 cm, about 4 cm, about 5 cm, about 10 cm, about 20 cm, about 30 cm, about 40 cm, about 50 cm, about 60 cm, about 70 cm, about 80 cm, about 90 cm, about 1 m, about 2 m, about 3 m, about 4 m, about 5 m, about 6 m, about 7 m, about 8 m, about 9 m, about 10 m, about 20 m, about 30 m, about 40 m, about 50 m, about 60 m, about 70 m, about 80 m, about 90 m, or about 100 m.

(52) The separator coating the anode material can prevent electrolyte from evaporating during conveyance or other portions of the production process. By covering the surface of the anode material distal to the anode current collector a significant percentage of the surface of the anode material (e.g., 90-95%) is not exposed to the surrounding environment. Thus, a significant portion of the avenues for evaporation are restricted.

(53) Step 14 includes disposing the cathode material onto the cathode current collector. In some embodiments, the dispensation of the cathode material can have the same or substantially similar properties to those described above with reference to the anode material in step 11. Step 15 includes disposing the second separator onto the cathode material. In some embodiments, the disposal of the second separator onto the cathode material can have the same or substantially similar properties to those described above with reference to the first separator in step 12.

(54) Step 16 optionally includes conveying the cathode. In some embodiments, the duration and distance of the conveying of the cathode can be the same or substantially similar to the duration and distance of the conveying of the anode with reference to step 13. In some embodiments, the cathode can be conveyed on the same conveyor as the anode. In some embodiments, the anode can be conveyed on a first conveyor and the cathode can be conveyed on a second conveyor, the second conveyor different from the first conveyor.

(55) Step 17 optionally includes wetting the first separator and/or the second separator. The wetting can be via a wetting agent. In some embodiments, the wetting agent can include an electrolyte solvent without electrolyte salt. In some embodiments, the wetting agent can include an electrolyte solution. In some embodiments, the wetting agent can include a diluted electrolyte solution (i.e., an electrolyte solution with a salt concentration lower than the targeted salt concentration in the finished electrochemical cell). In some embodiments, the wetting agent can have an electrolyte salt concentration of at least about 0.1 M, at least about 0.2 M, at least about 0.3 M, at least about 0.4 M, at least about 0.5 M, at least about 0.6 M, at least about 0.7 M, at least about 0.8 M, or at least about 0.9 M. In some embodiments, the wetting agent can have an electrolyte salt concentration of no more than about 1 M, no more than about 0.9 M, no more than about 0.8 M, no more than about 0.7 M, no more than about 0.6 M, no more than about 0.5 M, no more than about 0.4 M, no more than about 0.3 M, no more than about 0.2 M. Combinations of the above-referenced concentrations of electrolyte salt in the wetting agent are also possible (e.g., at least about 0.1 M and no more than about 1 M or at least about 0.4 M and no more than about 0.6 M), inclusive of all values and ranges therebetween. In some embodiments, the wetting agent can have an electrolyte salt concentration of about 0.1 M, about 0.2 M, about 0.3 M, about 0.4 M, about 0.5 M, about 0.6 M, about 0.7 M, about 0.8 M, about 0.9 M, or about 1 M.

(56) In some embodiments, the electrolyte solvent can include ethyl methyl carbonate (EMC), ethylene carbonate (EC), propylene carbonate (PC), dimethyl carbonate (DMC), butylene carbonate, and their chlorinated or fluorinated derivatives, and/or a family of acyclic dialkyl carbonate esters, such as dimethyl carbonate, diethyl carbonate, ethylmethyl carbonate, dipropyl carbonate, methyl propyl carbonate, ethyl propyl carbonate, dibutyl carbonate, butylmethyl carbonate, butylethyl carbonate and butylpropyl carbonate. In some embodiments, the electrolyte

solvent can include gamma-Butyrolactone (GBL), dimethoxyethane, tetrahydrofuran, 2-methyl tetrahydrofuran, 1,3-dioxolane, 1,4-dioxane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methylsulfolane, acetonitrile, propionitrile, ethyl acetate, methyl propionate, ethyl propionate, dimethyl carbonate, tetraglyme, monoglyme, dioxane, or any other suitable electrolyte solvent. In some embodiments, the electrolyte salt can include LiClO_4 , LiPF_6 , LiBF_4 , LiTFSI , LiBETI , LiBOB , Lithium difluoro (oxalato) borate (LiODFB), Lithium bis(fluorosulfonyl)imide (LiFSI), or any other appropriate electrolyte salt.

(57) In some embodiments, the wetting agent can be sprayed onto the first separator and/or the second separator. In some embodiments, the wetting agent can be brushed onto the first separator and/or the separator. In some embodiments, the wetting agent can be applied to the first separator via a first method and the second separator via a second method, the second method different from the first method. In some embodiments, the wetting agent can aid in adhering the separators to their respective electrode materials.

(58) In some embodiments, less than about 20%, less than about 19%, less than about 18%, less than about 17%, less than about 16%, less than about 15%, less than about 14%, less than about 13%, less than about 12%, less than about 11%, less than about 10%, less than about 9%, less than about 8%, less than about 7%, less than about 6%, less than about 5%, less than about 4%, less than about 3%, less than about 2%, or less than about 1% by volume of the wetting agent can be lost to evaporation during execution of the method **10**.

(59) In some embodiments, less than about 20%, less than about 19%, less than about 18%, less than about 17%, less than about 16%, less than about 15%, less than about 14%, less than about 13%, less than about 12%, less than about 11%, less than about 10%, less than about 9%, less than about 8%, less than about 7%, less than about 6%, less than about 5%, less than about 4%, less than about 3%, less than about 2%, or less than about 1% by volume of the electrolyte solution in the anode material can be lost to evaporation during execution of the method.

(60) In some embodiments, less than about 20%, less than about 19%, less than about 18%, less than about 17%, less than about 16%, less than about 15%, less than about 14%, less than about 13%, less than about 12%, less than about 11%, less than about 10%, less than about 9%, less than about 8%, less than about 7%, less than about 6%, less than about 5%, less than about 4%, less than about 3%, less than about 2%, or less than about 1% by volume of the electrolyte solution in the cathode material can be lost to evaporation during execution of the method.

(61) In some embodiments, less than about 20%, less than about 19%, less than about 18%, less than about 17%, less than about 16%, less than about 15%, less than about 14%, less than about 13%, less than about 12%, less than about 11%, less than about 10%, less than about 9%, less than about 8%, less than about 7%, less than about 6%, less than about 5%, less than about 4%, less than about 3%, less than about 2%, or less than about 1% by volume of the combination of the electrolyte solution in the anode material, the electrolyte solution in the cathode material, and the wetting agent can be lost to evaporation during execution of the method.

(62) In some embodiments, the anode material, the anode current collector, and the first separator can be disposed in a first package as an anode kit. In some embodiments, the cathode material, the cathode current collector, and the second separator can be disposed in a second package as a cathode kit. In some embodiments, the first separator can be wetted prior to disposal in the first package. In some embodiments, the second separator can be wetted prior to disposal in the second package.

(63) Step **18** includes coupling the first separator to the second separator to form the electrochemical cell. In some embodiments, the coupling can include adhering the first separator to the second separator. In some embodiments, the first separator and/or the second separator can be wetted to facilitate the adhering of the first separator to the second separator. In some embodiments, the anode material, the anode current collector, and the first separator can be removed from the first package prior to coupling the first separator to the second separator to form

the electrochemical cell. In some embodiments, the cathode material, the cathode current collector, and the second separator can be removed from the second package prior to coupling the first separator to the second separator. In some embodiments, a semi-solid electrode material can be applied to the first separator and/or the second separator prior to coupling the first separator to the second separator, such that the semi-solid electrode material is disposed between the first separator and the second separator in the electrochemical cell. In some embodiments, a conventional electrode material can be applied to the first separator and/or the second separator prior to coupling the first separator to the second separator, such that the conventional electrode material is disposed between the first separator and the second separator in the electrochemical cell. In some embodiments, a solid-state electrolyte material can be applied to the first separator and/or the second separator prior to coupling the first separator to the second separator, such that the solid-state electrolyte material is disposed between the first separator and the second separator in the electrochemical cell.

(64) FIGS. 4A-4C show conveyance of electrodes, according to various embodiments. FIGS. 4A-4C show an anode material **410** disposed on an anode current collector **420** and being conveyed by a first conveyor **90a**, and a cathode material **430** disposed on a cathode current collector **440** and being conveyed by a second conveyor **90b**. FIG. 4A shows the electrodes without any separators disposed thereon. As shown in FIG. 4A, electrolyte solvent ES evaporates from both of the electrodes. FIG. 4B shows a first separator **450a** disposed on the anode material **410**. As shown in FIG. 4B, electrolyte solvent ES evaporates from the cathode material **430** but evaporation of electrolyte solvent ES from the anode material **410** is eliminated or significantly reduced. FIG. 4B shows the first separator **450a** disposed on the anode material **410** and a second separator **450b** disposed on the cathode material **430**. As shown in FIG. 4C, evaporation of electrolyte solvent ES from both the anode material **410** and the cathode material **430** is eliminated or significantly reduced. As shown, the first conveyor **90a** is a separate conveyor from the second conveyor **90b**. In some embodiments, the anode material **410**, the anode current collector **420**, the cathode material **430**, and the cathode current collector **440** can all be conveyed on the same conveyor.

(65) FIG. 5 shows an illustration of an electrochemical cell **500**, according to an embodiment. The electrochemical cell **500** is substantially similar to the electrochemical cell **200**, and includes an anode material **510** disposed on an anode current collector **520**, a cathode material **530** disposed on a cathode current collector **540**, a first separator **550a** disposed on the anode material **510**, and a second separator **550b** disposed on the cathode material **530**, which can be substantially similar to the anode material **210**, the anode current collector **220**, the cathode material **230**, the cathode current collector **240**, the first separator **250a**, and the second separator **250b**, respectively, as previously described herein with respect to the electrochemical cell **200**.

(66) However, different from electrochemical cell **200**, the electrochemical cell **500** also includes a third separator **550c** disposed between the first separator **550a** and the second separator **550b**. A first interlayer **560a** is disposed between the first separator **550a** and the third separator **550c**, and a second interlayer **560b** is disposed between the second separator **550b** and the third separator **550c**. The third separator **550c** may be substantially similar to the first separator **250a** and/or the second separator **250b** as described in detail with respect to the electrochemical cell **200**.

(67) In some embodiments, the first interlayer **560a** and/or the second interlayer **560b** can include an electrolyte layer, as described in detail with respect to FIG. 2. In some embodiments, the electrolyte layer can partially or fully saturate the first separator **550a**, the second separator **550b**, and or the third separator **550** (collectively referred to as the separators **550**). In some embodiments, the electrolyte layer can aid in bonding the first separator **550a** and second separator **550b** to the third separator **550c**. In some embodiments, the electrolyte layer can create a surface tension to bond the first separator **550a** and the second separator **550b** to the third separator **550c**. In some embodiments, the electrolyte layer can facilitate movement of electroactive species between the anode material **510** and the cathode material **530**.

(68) In some embodiments, the first interlayer **560a** and/or the second interlayer **560b** can have any thickness as described in detail with respect to the interlayer **260** of the electrochemical cell **200**. In some embodiments, the first interlayer **560a** and the second interlayer can include a semi-solid electrode layer disposed between the first separator **550a** and third separator **550c**, and the second separator **550b** and the third separator **550c**, respectively. In some embodiments, the layer of semi-solid electrode material can be included in addition to the electrolyte layer. In some embodiments, the semi-solid electrode layer between the first separator **550a** and the third separator **550c**, and/or between the second separator **550b** and the third separator **550c** can include a material that reacts with metallic lithium. In some embodiments, the semi-solid electrode layer between the first separator **550a** and the third separator **550c**, and/or between the second separator **550b** and the third separator **550c** can include hard carbon, graphite, or any other suitable electrode material or combinations thereof. In some embodiments, if the anode material **510** begins to form dendrites that penetrate the first separator **550a**, the dendritic material can react with the semi-solid electrode layer between the first separator **550a** and the third separator **550b**, such that the dendrites dissipate, thus preventing a short circuit. In some embodiments, one or more of the first separator **550a**, the second separator **550b**, and the third separator **550c** may include solid-state electrolyte sheets.

(69) In some embodiments, the semi-solid electrode layer can aid in transporting electroactive species across the separators **550**, and/or provide reduced tortuosity and better lithium ion diffusion compared to conventional electrode materials. The composition of the semi-solid electrode layer(s) can be fine-tuned to facilitate ion movement therethrough. In some embodiments, the semi-solid electrode layer between the first separator **550a** and third separator **550c**, and/or between the second separator **550b** and the third separator **550c** can have catalytic effects to remove, dissolve, and/or corrode contaminating metal powders (e.g., iron, chromium, nickel, aluminum, copper). In such cases, the semi-solid electrode layer(s) can serve as a metal contamination removing buffer layer. In some embodiments, the semi-solid electrode layer(s) can include a non-lithium ion semi-solid slurry with an aligned pore structure, a high surface area, and/or a diffusive structure combined with an electrolyte. Such materials can include metal-organic frameworks (MOFs), carbon black, an anode aluminum oxide (AAO) template, and/or silica. In such cases, the semi-solid electrode layer(s) can serve as an electrolyte reservoir and/or an embedding base for a dendrite-removing catalyst. Such materials can also improve current distributions in the electrochemical cell **250**. In some embodiments, the dendrite-removing catalyst can include a metal base and/or a polymer base for the facilitation of redox reactions. In some embodiments, the dendrite-removing catalyst can include fluorine, sulfide, or any other suitable catalyst or combinations thereof. In some embodiments, the catalyst can include a base polymer coating mix or a carbon mix.

(70) In some embodiments, the interlayers **560a** and/or **560b** can include a conventional (i.e., solid) electrode layer disposed between the first separator **550a** and the third separator **550c**, and/or the second separator **550b** and the third separator **550c**, respectively. In some embodiments, the conventional electrode layer between the respective separators **550** can include a binder (e.g., a solid binder or a gel binder).

(71) In some embodiments, the interlayers **560a** and/or **560b** can include a polyolefin, a solid-state electrolyte sheet, and/or a polymer electrolyte sheet. In some embodiments, the interlayers **560a** and/or **560b** can include polyacrylonitrile (PAN), poly(vinylidene fluoride-co-hexafluoropropylene) (PVDF-HFP), poly(methyl methacrylate) (PMMA), polyacrylic acid (PAA), polyethylene oxide (PEO), or any combination thereof.

(72) In some embodiments, the interlayers **560a** and/or **560b** can include a cathode. In some embodiments, the cathode in the interlayers **560a** and/or **560b** can include lithium titanate (LTO), hard carbon (HC), and/or any other material with a high impedance connection. In some embodiments, the LTO can include an electron-conductive LTO, such as

Li.sub.4+xTi.sub.5O.sub.12 and/or Li.sub.4Ti.sub.5O.sub.12-x. In some embodiments, the interlayers **560a** and/or **560b** can include lithium iron phosphate (LFP) with a high impedance connection. The LFP can be considered a safe chemistry for the monitoring of dendrite formation. If a dendrite forms in either of the electrodes and penetrates into the interlayers **560a** and/or **560b**, the dendrite would be consumed. Also, voltage can be monitored between the first interlayer **560a** and the anode current collector **520**, as shown. In some embodiments, voltage can be monitored between the second interlayer **560b** and the cathode current collector **540**. This voltage monitoring can detect if a dendrite has reached the interlayers **560a** and/or **560b**.

(73) Measuring voltage between the first interlayer **560a** and the anode current collector **520** and/or the second interlayer **560b** and the cathode current collector **540** can be a more efficient method of detecting defects in the electrochemical cell **500** than measuring across the entire electrochemical cell **500** (i.e., between the anode current collector **520** and the cathode current collector **540**), particularly in modules with multiple cells. In some embodiments, multiple electrochemical cells can be connected in parallel and/or series to produce a cell module. For example, if a cell has a capacity of 3 Ah, 50 such cells can be connected in parallel to produce a capacity of 150 Ah. In some embodiments, the module can include about 1, about 2, about 3, about 4, about 5, about 6, about 7, about 8, about 9, about 10, about 11, about 12, about 13, about 14, about 15, about 16, about 17, about 18, about 19, about 20, about 25, about 30, about 35, about 40, about 45, about 50, about 55, about 60, about 65, about 70, about 75, about 80, about 85, about 90, about 95, or about 100 electrochemical cells connected in series and/or parallel, inclusive of all values and ranges therebetween. In monitoring the voltage across the first interlayer **560a** and the anode current collector **520** and/or the second interlayer **560b** and the cathode current collector **540**, the first interlayer **560a** and/or the second interlayer **560b** can serve as a reference electrode.

(74) In some embodiments, individual electrochemical cell in a module can have a capacity of about 0.5 Ah, about 1 Ah, about 2 Ah, about 3 Ah, about 4 Ah, about 5 Ah, about 6 Ah, about 7 Ah, about 8 Ah, about 9 Ah, or about 10 Ah, inclusive of all values and ranges therebetween. In some embodiments, modules described herein can have a capacity of about 10 Ah, about 20 Ah, about 30 Ah, about 40 Ah, about 50 Ah, about 60 Ah, about 70 Ah, about 80 Ah, about 90 Ah, about 100 Ah, about 110 Ah, about 120 Ah, about 130 Ah, about 140 Ah, about 150 Ah, about 160 Ah, about 170 Ah, about 180 Ah, about 190 Ah, about 200 Ah, about 210 Ah, about 220 Ah, about 230 Ah, about 240 Ah, about 250 Ah, about 260 Ah, about 270 Ah, about 280 Ah, about 290 Ah, or about 300 Ah, inclusive of all values and ranges therebetween.

(75) In some embodiments, only one of the first interlayer **560a** and the second interlayer **560b** may be connected or coupled to an electrical source or sink. For example, in some embodiments, the first interlayer **560a** (e.g., a graphite layer, a hard carbon layer, or any other material described herein) may not be connected with cathode, neutral, or ground, while the second interlayer **560b** (e.g., a graphite layer, a hard carbon layer, or any other material described herein) may be coupled or connected to a cathode or neutral (e.g., via a diode or high resistance). In some embodiments, a current collector of any other layer may extend between the first separator **550a** and the second separator **550b** to serve as the third separator **550c**, any may be employed as a shutdown separator. In some embodiments, the current collector of the other layer may be formed from aluminum, gold, platinum, stainless steel, titanium foil, conductive ink, etc. In some embodiments, the current collector may be formed or processed by lamination, printing (e.g., inkjet printing, gravure printing, screen printing, etc.), sputtering, spray coating, or deposition, or any other suitable method on the separator or any other suitable method. In some embodiments, a tab may be coupled to the current collector that forms one of the interlayers **560a/b**, or directly to the interlayer **560a** or **560b** that does include a current collector (e.g., a graphite or hard carbon layer). In other embodiments, the tab may be formed monolithically with the current collector or otherwise interlayer **560** having a portion thereof disposed outside the electrochemical cell **500**.

(76) FIG. 6 shows an illustration of an electrochemical cell **600**, according to an embodiment. The

electrochemical cell **600** is substantially similar to the electrochemical cell **200**, and includes an anode material **610** disposed on an anode current collector **620**, a cathode material **630** disposed on a cathode current collector **640**, a first separator **650a** disposed on the anode material **610**, a second separator **650b** disposed on the cathode material **630**, and an interlayer **660** disposed between the first separator **650a** and the second separator **650b**. In some embodiments, the anode material **610**, the anode current collector **620**, the cathode material **630**, the cathode current collector **640**, and the interlayer **660** can be the same or substantially similar to the anode material **210**, the anode current collector **220**, the cathode material **230**, the cathode current collector **240**, and the interlayer **260**, as described above with reference to FIG. 2. Thus, certain aspects of the anode material **610**, the anode current collector **620**, the cathode material **630**, the cathode current collector **640**, and the interlayer **660** are not described in greater detail herein.

(77) Different from the electrochemical cell **200**, the first separator **650a** and/or the second separator **650b** may include multiple layers. For example, as shown in FIG. 6, the first separator **650a** includes a first separator first layer **650a1** and a first separator second layer **650a2** that are formed from different materials (e.g., any of the materials described with respect to the separators **260a** and **260b**). Similarly, the second separator **650b** includes a second separator first layer **650b1** and a second separator second layer **650b2** that are formed from different materials (e.g., any of the materials described with respect to the separators **260a** and **260b**). The first separator second layer **650a2** and the second separator second layer **650b2** is disposed proximate to the interlayer **660** such that the interlayer **660** is interposed between the first separator second layer **650a2** and the second separator second layer **650b2**. The interlayer **660** may include a semisolid interlayer, may include a binder, or may include any other interlayer as described with respect to the interlayer **260**. In some embodiments, the first separator first layer **650a1** and the second separator first layer **650b1** may be formed from polypropylene. In some embodiments, the first separator second layer **650a2** and the second separator second layer **650b2** may be formed from polyethylene. In other embodiments, the first separator first and/or second layers **650a1** and **650a2**, and/or the second separator first and second layers **650b1** and/or **650b2** may be formed from any other material as described herein. In some embodiments, axial end regions **670** of the first separator **650a** and/or the second separator **650b** that extend beyond an axial extent of the interlayer **660** may be bonded, adhered, welded, or otherwise coupled to each other so as to form a sealed pocket or cavity within which the interlayer **660** is disposed. This may advantageously prevent a semisolid or slurry based interlayer **660** from leaking from between the first separator **650a** and the second separator **650b**.

(78) FIG. 7 shows an illustration of an electrochemical cell **700**, according to an embodiment. The electrochemical cell **700** is substantially similar to the electrochemical cell **200**, and includes an anode material **710** disposed on an anode current collector **720**, a cathode material **730** disposed on a cathode current collector **740**, a first separator **750a** disposed on the anode material **710**, a second separator **750b** disposed on the cathode material **730**, and an interlayer **760** disposed between the first separator **750a** and the second separator **750b**. In some embodiments, the anode material **710**, the anode current collector **720**, the cathode material **730**, the cathode current collector **740**, the first separator **750a** and the second separator **750b** can be the same or substantially similar to the anode material **210**, the anode current collector **220**, the cathode material **230**, the cathode current collector **240**, the first current collector **250a**, and the second collector **250b**, as described above with reference to FIG. 2. Thus, certain aspects of the anode material **710**, the anode current collector **720**, the cathode material **730**, the cathode current collector **740**, the first separator **750a**, and the second separator **750b** are not described in greater detail herein.

(79) In some embodiment, the interlayer **760** is a multilayer structure. For example, as shown in FIG. 7, the interlayer **760** includes a first layer **760a** that may include a solid-state electrolyte, for example, any of the solid-state electrolytes as described with respect to FIG. 2. The interlayer **760** may optionally, also include a second layer **760b** disposed between the first layer **760a** and the first separator **750a**, and a third layer **760c** disposed between the first layer **760a** and the second

separator **750b**. In some embodiments, the second layer **760b** and/or the third layer **760c** may include a cathode, for example, LTO, hard carbon, LFP, and/or any other material with a high impedance connection, as described in detail with respect to FIG. 2. For example, the second layer **760b** may include hard carbon, and the third layer **760c** may include LFP. The second layer **760b** may be coupled to the anode current collector **720** via a first discharge protection component **780a** (e.g., a diode, a high resistance resistor, or any other suitable structure) and the third layer **760c** may be coupled to the cathode current collector **740** via a second discharge protection component **780b** (e.g., a diode, a high resistance resistor, or any other suitable structure). As previously described, an iron dendrite can grow and touch hard carbon, graphite, and/or other carbon-containing materials in the interlayer **760**, with the interlayer **760** having an anode potential in the second layer **760b** and a cathode potential in the third layer **760c**. Once the iron dendrite touches the hard carbon, graphite, and/or the other carbon-containing materials in the interlayer **760**, the iron dissolves under the cathode potential, but the high current moving through the electrochemical cell **700** persists via a connection through the discharge protection components **780a** and **780b**. When metal contamination is used to prevent dangerous short circuit events, voltage can be monitored between the interlayer **760** and the anode current collector **720** and/or the cathode current collector **740**, as described with respect to FIG. 2.

Examples

(80) Comparative Example 1: A lithium-copper cell was constructed (referred to herein as “Comp Ex 1”). Lithium was plated onto copper foil. The cell was cycled at 1 mA/cm² for 1 hour at 25° C. under a pressure of 200 psig. Stripping of the copper foil continued until a 1V cut-off was reached. A standard separator including a single layer (i.e., a single separator) was placed between the lithium foil anode and the copper foil cathode.

(81) Example 1: A lithium-copper cell was constructed (referred to herein as “Ex 1”). Lithium was plated onto copper foil. The cell was cycled at 1 mA/cm² for 1 hour at 25° C. under a pressure of 200 psig. Stripping of the copper foil continued until a 1V cut-off was reached. A separator coated with a layer of hard carbon (Kuraray HC, 2-3 μm) was coupled to a standard separator and placed between the lithium foil anode and the copper foil cathode, the hard carbon layer facing the anode. The hard carbon coated separator was implemented as a means of lithiating and/or complexing with any dendritic lithium that protrudes from the lithium foil surface, enabling a safety feature to prevent a hard short from lithium plating on the anode.

(82) Both Comp Ex 1 and Ex 1 were subject to 32 cycles before deconstruction, where lithium was stripped from the copper foil, allowing lithium to complex with the hard carbon in the Ex 1 cell. The hard carbon in the active area of lithium appeared shiny, indicating lithiation of the hard carbon. The hard carbon that was outside of the lithium foil contact area was dull in color, suggesting it was unlithiated. The cycled lithium foil anode also appeared pristine in nature, indicating the lithium was being plated on the hard carbon. No mossy or dendritic lithium was observed on the foil. FIG. 8A-8B show supporting voltage profiles highlighting the difference in overpotential of Comp Ex 1 (FIG. 8A) vs. Ex 1 (FIG. 8B). As shown, Ex 1 with a hard carbon layer between two separators, experiences less significant overpotential losses than Comp Ex 1.

(83) Comparative Example 2: A lithium copper cell was constructed (referred to herein as “Comp. Ex. 2”) and operated similar to Comp. Ex. 1, except that Comp. Ex. 2 was cycled at 7.5 mA/cm² with 75% lithium ion usage.

(84) Example 2: A lithium copper cell was constructed (referred to herein as “Ex. 2”) and operated similar to Ex. 1, except that Ex. 2 was cycled at 7.5 mA/cm² with 75% lithium ion usage. FIGS. 9A and 9B show supporting voltage profiles highlighting the difference in overpotential of Comp. Ex. 2 and Ex. 2. The Comp. Ex. 2 cell that did not include the interlayer shorted in 11 cycles within 22 hours, while the Ex. 2 cell that included the hard carbon interlayer continued to operate normally after 25 cycles with minimum over polarization. This indicates that the interlayer smooths or levels the current distribution for fast lithium plating, storing, and preventing the dendrite from

projecting through the separators.

(85) As used in this specification, the singular forms “a,” “an,” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, the term “a member” is intended to mean a single member or a combination of members, “a material” is intended to mean one or more materials, or a combination thereof.

(86) The term “substantially” when used in connection with “cylindrical,” “linear,” and/or other geometric relationships is intended to convey that the structure so defined is nominally cylindrical, linear or the like. As one example, a portion of a support member that is described as being “substantially linear” is intended to convey that, although linearity of the portion is desirable, some non-linearity can occur in a “substantially linear” portion. Such non-linearity can result from manufacturing tolerances, or other practical considerations (such as, for example, the pressure or force applied to the support member). Thus, a geometric construction modified by the term “substantially” includes such geometric properties within a tolerance of plus or minus 5% of the stated geometric construction. For example, a “substantially linear” portion is a portion that defines an axis or center line that is within plus or minus 5% of being linear.

(87) As used herein, the term “set” and “plurality” can refer to multiple features or a singular feature with multiple parts. For example, when referring to a set of electrodes, the set of electrodes can be considered as one electrode with multiple portions, or the set of electrodes can be considered as multiple, distinct electrodes. Additionally, for example, when referring to a plurality of electrochemical cells, the plurality of electrochemical cells can be considered as multiple, distinct electrochemical cells or as one electrochemical cell with multiple portions. Thus, a set of portions or a plurality of portions may include multiple portions that are either continuous or discontinuous from each other. A plurality of particles or a plurality of materials can also be fabricated from multiple items that are produced separately and are later joined together (e.g., via mixing, an adhesive, or any suitable method).

(88) As used herein, the term “semi-solid” refers to a material that is a mixture of liquid and solid phases, for example, such as a particle suspension, a slurry, a colloidal suspension, an emulsion, a gel, or a micelle.

(89) Various concepts may be embodied as one or more methods, of which at least one example has been provided. The acts performed as part of the method may be ordered in any suitable way. Accordingly, embodiments may be constructed in which acts are performed in an order different than illustrated, which may include performing some acts simultaneously, even though shown as sequential acts in illustrative embodiments. Put differently, it is to be understood that such features may not necessarily be limited to a particular order of execution, but rather, any number of threads, processes, services, servers, and/or the like that may execute serially, asynchronously, concurrently, in parallel, simultaneously, synchronously, and/or the like in a manner consistent with the disclosure. As such, some of these features may be mutually contradictory, in that they cannot be simultaneously present in a single embodiment. Similarly, some features are applicable to one aspect of the innovations, and inapplicable to others.

(90) In addition, the disclosure may include other innovations not presently described. Applicant reserves all rights in such innovations, including the right to embodiment such innovations, file additional applications, continuations, continuations-in-part, divisionals, and/or the like thereof. As such, it should be understood that advantages, embodiments, examples, functional, features, logical, operational, organizational, structural, topological, and/or other aspects of the disclosure are not to be considered limitations on the disclosure as defined by the embodiments or limitations on equivalents to the embodiments. Depending on the particular desires and/or characteristics of an individual and/or enterprise user, database configuration and/or relational model, data type, data transmission and/or network framework, syntax structure, and/or the like, various embodiments of the technology disclosed herein may be implemented in a manner that enables a great deal of flexibility and customization as described herein.

(91) All definitions, as defined and used herein, should be understood to control over dictionary definitions, definitions in documents incorporated by reference, and/or ordinary meanings of the defined terms.

(92) As used herein, in particular embodiments, the terms “about” or “approximately” when preceding a numerical value indicates the value plus or minus a range of 10%. Where a range of values is provided, it is understood that each intervening value, to the tenth of the unit of the lower limit unless the context clearly dictates otherwise, between the upper and lower limit of that range and any other stated or intervening value in that stated range is encompassed within the disclosure. That the upper and lower limits of these smaller ranges can independently be included in the smaller ranges is also encompassed within the disclosure, subject to any specifically excluded limit in the stated range. Where the stated range includes one or both of the limits, ranges excluding either or both of those included limits are also included in the disclosure.

(93) The phrase “and/or,” as used herein in the specification and in the embodiments, should be understood to mean “either or both” of the elements so conjoined, i.e., elements that are conjunctively present in some cases and disjunctively present in other cases. Multiple elements listed with “and/or” should be construed in the same fashion, i.e., “one or more” of the elements so conjoined. Other elements may optionally be present other than the elements specifically identified by the “and/or” clause, whether related or unrelated to those elements specifically identified. Thus, as a non-limiting example, a reference to “A and/or B”, when used in conjunction with open-ended language such as “comprising” can refer, in one embodiment, to A only (optionally including elements other than B); in another embodiment, to B only (optionally including elements other than A); in yet another embodiment, to both A and B (optionally including other elements); etc.

(94) As used herein in the specification and in the embodiments, “or” should be understood to have the same meaning as “and/or” as defined above. For example, when separating items in a list, “or” or “and/or” shall be interpreted as being inclusive, i.e., the inclusion of at least one, but also including more than one, of a number or list of elements, and, optionally, additional unlisted items. Only terms clearly indicated to the contrary, such as “only one of” or “exactly one of,” or, when used in the embodiments, “consisting of,” will refer to the inclusion of exactly one element of a number or list of elements. In general, the term “or” as used herein shall only be interpreted as indicating exclusive alternatives (i.e., “one or the other but not both”) when preceded by terms of exclusivity, such as “either,” “one of,” “only one of,” or “exactly one of.” “Consisting essentially of,” when used in the embodiments, shall have its ordinary meaning as used in the field of patent law.

(95) As used herein in the specification and in the embodiments, the phrase “at least one,” in reference to a list of one or more elements, should be understood to mean at least one element selected from any one or more of the elements in the list of elements, but not necessarily including at least one of each and every element specifically listed within the list of elements and not excluding any combinations of elements in the list of elements. This definition also allows that elements may optionally be present other than the elements specifically identified within the list of elements to which the phrase “at least one” refers, whether related or unrelated to those elements specifically identified. Thus, as a non-limiting example, “at least one of A and B” (or, equivalently, “at least one of A or B,” or, equivalently “at least one of A and/or B”) can refer, in one embodiment, to at least one, optionally including more than one, A, with no B present (and optionally including elements other than B); in another embodiment, to at least one, optionally including more than one, B, with no A present (and optionally including elements other than A); in yet another embodiment, to at least one, optionally including more than one, A, and at least one, optionally including more than one, B (and optionally including other elements); etc.

(96) In the embodiments, as well as in the specification above, all transitional phrases such as “comprising,” “including,” “carrying,” “having,” “containing,” “involving,” “holding,” “composed of,” and the like are to be understood to be open-ended, i.e., to mean including but not limited to.

Only the transitional phrases “consisting of” and “consisting essentially of” shall be closed or semi-closed transitional phrases, respectively, as set forth in the United States Patent Office Manual of Patent Examining Procedures, Section 2111.03.

(97) While specific embodiments of the present disclosure have been outlined above, many alternatives, modifications, and variations will be apparent to those skilled in the art. Accordingly, the embodiments set forth herein are intended to be illustrative, not limiting. Various changes may be made without departing from the spirit and scope of the disclosure. Where methods and steps described above indicate certain events occurring in a certain order, those of ordinary skill in the art having the benefit of this disclosure would recognize that the ordering of certain steps may be modified and such modification are in accordance with the variations of the invention. Additionally, certain of the steps may be performed concurrently in a parallel process when possible, as well as performed sequentially as described above. The embodiments have been particularly shown and described, but it will be understood that various changes in form and details may be made.

Claims

1. A method of forming an electrochemical cell, the method comprising: disposing a first electrode material onto a first current collector; disposing a second electrode material onto a second current collector; disposing a first separator on the first electrode material; disposing a second separator on the second electrode material; and disposing the first separator onto the second separator with an interlayer disposed therebetween, the interlayer having electron-conductive properties, the interlayer having a first layer including hard carbon and a second layer different from the first layer, the second layer including a cathode material, the first separator electrically isolating the first electrode material from the interlayer, the second separator electrically isolating the second electrode material from the interlayer.
2. The method of claim 1, wherein the second layer includes at least one of LFP, LTO, or NMC.
3. The method of claim 1, further comprising: dispensing an electrolyte solution onto at least one of the first separator or the second separator.
4. The method of claim 3, wherein the dispensing is via spraying.
5. The method of claim 1, wherein the interlayer is configured to prevent the projection of dendrites through at least one of the first separator or the second separator during operation of the electrochemical cell.
6. The method of claim 1, wherein the interlayer is configured to react with any dendritic material that has penetrated at least one of the first separator or the second separator such that the dendritic material dissipates, thus preventing a short circuit.
7. A method of forming an electrochemical cell, the method comprising: disposing a first electrode material onto a first current collector; disposing a second electrode material onto a second current collector; disposing a first electrically insulative separator on the first electrode material; disposing a second electrically insulative separator on the second electrode material; and disposing the first separator onto the second separator with an interlayer disposed therebetween, the interlayer comprising a first layer including a hard carbon material and a second layer different from the first layer, the second layer including a semi-solid electrode material, the interlayer further including a current collector material between the first layer and the second layer.
8. The method of claim 7, further comprising: dispensing an electrolyte solution onto at least one of the first separator or the second separator.
9. The method of claim 7, wherein the semi-solid electrode material includes at least one of LFP, LTO, or NMC.
10. The method of claim 7, wherein the interlayer is configured to prevent the projection of dendrites through at least one of the first separator or the second separator during operation of the

electrochemical cell.

11. The method of claim 1, wherein the interlayer has a thickness between about 500 nm and about 100 μm .
 12. The method of claim 1, wherein the interlayer includes an interlayer tab extending therefrom.
 13. The method of claim 7, wherein the interlayer has a thickness between about 500 nm and about 100 μm .
 14. The method of claim 7, wherein the interlayer includes an interlayer tab extending therefrom.
-