

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12406935
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Lee; Sang Youl et al.

Semiconductor device package

Abstract

A semiconductor device package includes a substrate; and a plurality of semiconductor structures disposed to be spaced apart from each other at a central portion of the substrate. Further, the semiconductor structure is disposed on the substrate and includes a first conductivity-type semiconductor layer, a second conductivity-type semiconductor layer disposed on the first conductivity-type semiconductor layer, and an active layer disposed between the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer. The semiconductor device package also includes a plurality of first interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the first conductivity-type semiconductor layer; and a plurality of second interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the second conductivity-type semiconductor layer.

Inventors: Lee; Sang Youl (Seoul, KR), Kang; Ki Man (Seoul, KR), Lee; Eun Dk (Seoul, KR)

Applicant: SUZHOU LEKIN SEMICONDUCTOR CO., LTD. (Suzhou, CN)

Family ID: 68100896

Assignee: SUZHOU LEKIN SEMICONDUCTOR CO., LTD. (Taicang, CN)

Appl. No.: 18/405806

Filed: January 05, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240222285 A1	Jul. 04, 2024

Foreign Application Priority Data

KR	10-2018-0039893	Apr. 05, 2018
KR	10-2018-0049083	Apr. 27, 2018

Related U.S. Application Data

continuation parent-doc US 16979734 US 11894307 WO PCT/KR2019/004032 20190405 child-doc US 18405806

Publication Classification

Int. Cl.: H01L23/538 (20060101); H01L25/075 (20060101); H10H20/857 (20250101)

U.S. Cl.:

CPC H01L23/5386 (20130101); H01L25/075 (20130101); H10H20/857 (20250101);

Field of Classification Search

CPC: H01L (33/00-648); H01L (25/075-0753)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
2004/0235210	12/2003	Tamura et al.	N/A	N/A
2011/0193123	12/2010	Moon	257/E33.072	H01L 33/382
2014/0048839	12/2013	Jeong et al.	N/A	N/A
2015/0262978	12/2014	Shibata	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2015-173222	12/2014	JP	N/A
2016-92235	12/2015	JP	N/A
10-2012-0114921	12/2011	KR	N/A
10-2014-0024580	12/2013	KR	N/A
10-2014-0032163	12/2013	KR	N/A
10-2015-0136852	12/2014	KR	N/A
10-2016-0059128	12/2015	KR	N/A
10-2018-0005896	12/2017	KR	N/A

OTHER PUBLICATIONS

Machine translation of KR 10-2016-0059128, published May 26, 2016 (Year: 2016). cited by applicant

Background/Summary

CROSS-REFERENCE TO RELATED PATENT APPLICATIONS (1) This application is a Continuation of copending application Ser. No. 16/979,734, filed on Sep. 10, 2020, which is a U.S. National Stage Application under 35 U.S.C. § 371 of PCT Application No. PCT/KR2019/004032, filed on Apr. 5, 2019, which claims priority to the Korean Application Nos. 10-2018-0039893 and 10-2018-0049083, filed on Apr. 5, 2018 and Apr. 27, 2018, respectively, all of which are hereby expressly incorporated by reference into the present application.

TECHNICAL FIELD

(1) The present invention relates to a semiconductor device package.

BACKGROUND ART

(2) Semiconductor devices including compounds such as GaN and AlGaN may be variously used as light-emitting devices, light-receiving devices, and various diodes due to many advantages thereof, such as wide and easily adjustable bandgap energy.

(3) In particular, light-emitting devices, such as light-emitting diodes and laser diodes, which use a III-V group or II-VI group compound semiconductor material, are capable of rendering various colors, such as red, green, and blue, and ultraviolet rays by virtue of the development of thin-film growth technologies and device materials, are capable of producing white light at high efficiency using fluorescent materials or through color mixing, and have advantages such as low power consumption, semi-permanent lifespan, fast response speed, safety, and environmental friendliness as compared with conventional light sources such as fluorescent lamps and incandescent lamps.

(4) In addition, when a light-receiving device such as a photodetector or a solar cell is manufactured using a III-V group or II-VI group compound semiconductor material, due to the development of an element material, the light-receiving device generates a photocurrent by absorbing light in various wavelength regions so that light in various wavelength regions from a gamma ray region to a radio wavelength region can be used. In addition, since the light-receiving device has advantages of having fast response speed, safety, environmental friendliness, and easy control of an element material, the light-receiving device can also be easily used for power control, microwave circuits, or communication modules.

(5) Accordingly, application of the semiconductor device has expanded to being applied as a transmission module of an optical communication device, a light-emitting diode (LED) backlight capable of replacing a cold cathode fluorescent lamp (CCFL) which constitutes a backlight of a liquid crystal display (LCD) device; a white LED lighting device capable of replacing a fluorescent lamp or an incandescent lamp; a headlight for a vehicle; a traffic light; a sensor for sensing gas or fire; and the like. In addition, the application of the semiconductor device may be expanded to a high frequency application circuit, another power control device, and a communication module.

(6) A plurality of light-emitting devices (chips) may be formed into a package and used as the headlight for a vehicle. In particular, recently, there is a rising interest in headlights in which a plurality of chips can be independently turned on.

(7) In this case, in order to make the plurality of chips appear as one light source, a distance between the chips should be minimized, but problems such as optical interference may occur. In addition, since a plurality of small-sized chips are disposed, there is a problem in that improving a contrast ratio is difficult when on/off-control is performed for each chip.

SUMMARY OF THE INVENTION

- (8) The present invention is directed to providing a semiconductor device package having an improved contrast ratio.
- (9) The present invention is also directed to providing a semiconductor device package having improved current spreading.
- (10) Problems to be solved in embodiments are not limited thereto, and objects and effects which may be determined from solutions to the problems and embodiments described below are also included.
- (11) According to an embodiment of the present invention, a semiconductor device package includes a substrate, and a plurality of semiconductor structures disposed to be spaced apart from each other at a central portion of the substrate, wherein the semiconductor structure is disposed on the substrate and includes a first conductivity-type semiconductor layer, a second conductivity-type semiconductor layer, and an active layer disposed between the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer, and a length ratio of a maximum height of an outermost surface of the first conductivity-type semiconductor layer to a separation distance between the adjacent semiconductor structures is in a range of 1:3 to 1:60.
- (12) The semiconductor structure may further include a channel layer at an edge thereof.
- (13) A side surface of the second conductivity-type semiconductor layer, a side surface of the active layer, and a lower surface of the first conductivity-type semiconductor layer may be exposed at the channel layer.
- (14) The maximum height of the outermost surface of the first conductivity-type semiconductor layer may be different from a height from an upper surface of the first conductivity-type semiconductor layer to an upper surface of the active layer.
- (15) An upper surface of the first conductivity-type semiconductor layer may include a first surface, a second surface disposed below the first surface, and an inclined surface positioned between the first surface and the second surface, and a height from a lower surface of the first conductivity-type semiconductor layer to the first surface may be greater than a height from the lower surface of the first conductivity-type semiconductor layer to the second surface.
- (16) The semiconductor device package may further include a plurality of first interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the first conductivity-type semiconductor layer, a plurality of second interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the second conductivity-type semiconductor layer, a first insulating layer disposed between the first interconnection line and the second interconnection line, a plurality of first pads each electrically connected to the first interconnection line, and a plurality of second pads each electrically connected to the second interconnection line.
- (17) The first interconnection line may include a first through-portion, which passes through the active layer, the second conductivity-type semiconductor layer, and the first insulating layer and is electrically connected to the first conductivity-type semiconductor layer, and a first end portion which extends to an edge of the substrate.
- (18) The second interconnection line may include a second end portion extending to the edge of the substrate.
- (19) The plurality of first pads and the plurality of second pads may be disposed along an edge of the substrate.**20**
- (20) The plurality of semiconductor structures may be disposed in a central portion of the plurality of first pads and the plurality of second pads.
- (21) The semiconductor device package may further include a channel layer disposed between the substrate and the semiconductor structure to expose portions of the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer.
- (22) The first electrode may be disposed on the first conductivity-type semiconductor layer exposed by the channel layer; and the second electrode may be disposed on the second

conductivity-type semiconductor layer exposed by the channel layer.

(23) According to an embodiment of the present invention, a display apparatus includes a semiconductor device package which includes a substrate, a plurality of semiconductor structures disposed to be spaced apart from each other at a central region of the substrate, a plurality of first interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to a first conductivity-type semiconductor layer, and a plurality of second interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to a second conductivity-type semiconductor layer, a plurality of data lines connected to the plurality of first interconnection lines, a plurality of scan lines connected to the plurality of second interconnection lines, a first driving unit connected to the plurality of data lines to provide a first control signal, a second driving unit connected to the plurality of scan lines to provide a second control signal, and a controller configured to determine the number of time divisions according to input data to provide the first control signal and the second control signal to the first driving unit and the second driving unit, wherein the semiconductor structure is disposed on the substrate and includes the first conductivity-type semiconductor layer, the second conductivity-type semiconductor layer, and an active layer disposed between the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer.

(24) A length ratio of a maximum height of an outermost surface of the first conductivity-type semiconductor layer to a separation distance between the adjacent semiconductor structures may be in a range of 1:3 to 1:60.

(25) According to an embodiment of the present invention, a semiconductor device package includes a substrate and a plurality of semiconductor structures disposed in a matrix form to be spaced apart from each other on the substrate, wherein the semiconductor structure is disposed on the substrate and includes a first conductivity-type semiconductor layer, a second conductivity-type semiconductor layer, and an active layer disposed between the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer, and wherein the semiconductor device package further includes an intermediate layer disposed on an outermost surface of the first conductivity-type semiconductor layer, and the intermediate layer overlaps the outermost surface of the first conductivity-type semiconductor layer in a direction perpendicular to a thickness direction thereof.

(26) The semiconductor structure may further include a channel layer at an edge thereof.

(27) A side surface of the second conductivity-type semiconductor layer, a side surface of the active layer, and a lower surface of the first conductivity-type semiconductor layer may be exposed at the channel layer.

(28) The outermost surface of the first conductivity-type semiconductor layer may be disposed between the lower surface of the first conductivity-type semiconductor layer and an upper surface of the first conductivity-type semiconductor layer.

(29) The intermediate layer may extend from the outermost surface of the first conductivity-type semiconductor layer to the upper surface of the first conductivity-type semiconductor layer.

(30) The semiconductor device package may further include a passivation layer disposed on the semiconductor structure.

(31) The intermediate layer may be disposed in at least one of a position between the passivation layer and an outer surface of the first conductivity-type semiconductor layer, a position inside the passivation layer, and a position on the passivation layer.

(32) The semiconductor device package may further include a plurality of first interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the first conductivity-type semiconductor layer, a plurality of second interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the second conductivity-type semiconductor layer, a first insulating layer disposed

between the first interconnection line and the second interconnection line, a plurality of first pads each electrically connected to the first interconnection line, and a plurality of second pads each electrically connected to the second interconnection line.

(33) The first interconnection line may include a first through-portion, which passes through the active layer, the second conductivity-type semiconductor layer, and the first insulating layer and is electrically connected to the first conductivity-type semiconductor layer, and a first end portion which extends to an edge of the substrate.

(34) The second interconnection line may include a second end portion extending to the edge of the substrate.

(35) The plurality of first pads and the plurality of second pads may be disposed along the edge of the substrate.

(36) The plurality of semiconductor structures may be disposed in a central portion of the plurality of first pads and the plurality of second pads.

(37) According to an embodiment of the present invention, a display apparatus includes a semiconductor device package which includes a substrate, a plurality of semiconductor structures disposed in a matrix form on the substrate, a plurality of first interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to a first conductivity-type semiconductor layer, and a plurality of second interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to a second conductivity-type semiconductor layer, a plurality of data lines connected to the plurality of first interconnection lines, a plurality of scan lines connected to the plurality of second interconnection lines, a first driving unit connected to the plurality of data lines to provide a first control signal, a second driving unit connected to the plurality of scan lines to provide a second control signal, and a controller configured to determine the number of time divisions according to input data to provide the first control signal and the second control signal to the first driving unit and the second driving unit, wherein the semiconductor structure is disposed on the substrate and includes the first conductivity-type semiconductor layer, the second conductivity-type semiconductor layer, and an active layer disposed between the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer, the semiconductor device package further includes an intermediate layer disposed on an outermost surface of the first conductivity-type semiconductor layer, and the intermediate layer overlaps the outermost surface of the first conductivity-type semiconductor layer in a direction perpendicular to a thickness direction thereof.

Advantageous Effects

(38) According to embodiments, it is possible to implement a semiconductor device package having an improved contrast ratio.

(39) In addition, it is possible to manufacture a semiconductor device package having improved current spreading.

(40) The various and advantageous advantages and effects of the present invention are not limited to the above description and may be more easily understood in the course of describing specific embodiments of the present invention.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 is a cross-sectional view of a semiconductor device package according to a first embodiment.

(2) FIG. 2 is a plan view of the semiconductor device package according to the first embodiment.

(3) FIG. 3 is a cross-sectional view taken along line M-M' in FIG. 2.

- (4) FIG. 4 is an enlarged view of region K in FIG. 3.
- (5) FIG. 5 is an enlarged view of region L in FIG. 3.
- (6) FIG. 6 is a graph showing a contrast ratio according to a maximum height of a side surface of a semiconductor structure.
- (7) FIG. 7 is a graph showing a contrast ratio according to a separation distance between adjacent semiconductor structures.
- (8) FIG. 8 is a view illustrating a first interconnection line in FIG. 2.
- (9) FIG. 9 is a view illustrating a second interconnection line in FIG. 2.
- (10) FIG. 10 is a cross-sectional view of a semiconductor device package according to a second embodiment.
- (11) FIG. 11 is a cross-sectional view of a semiconductor device package according to a third embodiment.
- (12) FIG. 12 is a cross-sectional view of the semiconductor device package according to the third embodiment corresponding to FIG. 3.
- (13) FIG. 13 is an enlarged view of region N in FIG. 12.
- (14) FIG. 14 is an enlarged view of region O in FIG. 12.
- (15) FIG. 15 is a graph showing a contrast ratio according to an intermediate layer.
- (16) FIG. 16 is a cross-sectional view of a semiconductor device package according to a fourth embodiment.
- (17) FIG. 17 is a cross-sectional view of a semiconductor device package according to a fifth embodiment.
- (18) FIGS. 18A to 18C are modified examples of FIG. 11.
- (19) FIG. 19 is a conceptual view illustrating a display apparatus according to an embodiment.
- (20) FIGS. 20A to 20M are views illustrating a method of manufacturing the semiconductor device package according to the first embodiment.
- (21) FIGS. 21A to 21D are views illustrating a method of manufacturing the semiconductor device package according to the third embodiment.

DETAILED DESCRIPTION OF THE EMBODIMENTS

(22) While the present invention is open to various modifications and alternative embodiments, specific embodiments thereof will be described and shown by way of example in the accompanying drawings. However, it should be understood that there is no intention to limit the present invention to the particular embodiments disclosed, and, on the contrary, the present invention is to cover all modifications, equivalents, and alternatives falling within the spirit and scope of the present invention.

(23) It should be understood that, although the terms including ordinal numbers such as first, second, and the like may be used herein to describe various elements, the elements are not limited by the terms. The terms are used only for the purpose of distinguishing one element from another. For example, without departing from the scope of the present invention, a second element could be termed a first element, and similarly a first element could be also termed a second element. The term “and/or” includes any one or all combinations of a plurality of associated listed items.

(24) In the case that one component is mentioned as being “connected” or “linked” to another component, it may be connected or linked to the corresponding component directly or other components may be present therebetween. On the other hand, in the case that one component is mentioned as being “directly connected” or “directly linked” to another component, it should be understood that other components are not present therebetween.

(25) It is to be understood that terms used herein are for the purpose of the description of particular embodiments and not for limitation. A singular expression includes a plural expression unless the context clearly indicates otherwise. It will be further understood that the terms “comprises” and/or “comprising,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof but do not preclude the presence or

addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

(26) Unless defined otherwise, all the terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which the present invention belongs. It will be further understood that the terms, such as those defined in commonly used dictionaries, should be interpreted as having meanings that are consistent with their meanings in the context of the relevant art and should not be interpreted in an idealized or overly formal sense unless expressly defined otherwise herein.

(27) Hereinafter, embodiments will be described in detail with reference to the accompanying drawings, the same or corresponding elements will be given the same reference numbers regardless of drawing symbols, and redundant descriptions will be omitted.

(28) A semiconductor device according to the present embodiment may be a light-emitting device.

(29) In the semiconductor device, electrons and holes recombine to emit light, and a wavelength of the light may be determined by an energy band gap inherent to a material. The emitted light may vary depending on a composition of the material.

(30) Hereinafter, embodiments of the present invention will be described in more detail with reference to the accompanying drawings so as to be easily realized by those skilled in the art.

(31) A semiconductor device according to the present embodiment may be a light-emitting device.

(32) In the semiconductor device, electrons and holes recombine to emit light, and a wavelength of the light may be determined by an energy band gap inherent to a material. The emitted light may vary depending on a composition of the material.

(33) Hereinafter, embodiments of the present invention will be described in more detail with reference to the accompanying drawings so as to be easily realized by those skilled in the art.

(34) FIG. 1 is a cross-sectional view of a semiconductor device package according to a first embodiment.

(35) Referring to FIG. 1, a semiconductor device package **100A** according to the first embodiment may include a substrate **170** and a plurality of semiconductor structures **120** disposed to be spaced apart from each other.

(36) The semiconductor device package **100A** may further include a bonding layer **171**, a channel layer **130**, a first electrode **141**, a second electrode **142**, a reflective layer **143**, a first interconnection line **151**, a second interconnection line **152**, a first insulating layer **161**, a second insulating layer **162**, a passivation layer **163**, a first pad **181**, and a second pad **182**.

(37) Here, it will be described below that FIG. 1 illustrates one semiconductor structure **120** disposed between the first pad **181** and the second pad **182** for convenience of description. However, as shown in FIG. 2, substantially, a plurality of semiconductor structures **120** (see FIG. 1) may be disposed to be spaced apart from each other by a predetermined distance on the substrate **170**, and the first pad **181** and the second pad **182** may be disposed to surround an edge of the substrate **170**.

(38) First, the semiconductor structure **120** may be disposed on the substrate **170**. The substrate **170** may serve to support the semiconductor structure **120**. The substrate **170** may include a material having a heat dissipation property. Therefore, a heat dissipation property may be improved through the substrate **170**. For example, the substrate **170** may include ceramic, but the present invention is not limited thereto. In particular, since a manufacturing process, package mounting, and heat dissipating of the semiconductor device package **100A** are easily performed due to the substrate **170**, reliability of an apparatus can be improved. However, the present invention is not necessarily limited thereto, and the substrate **170** may be a metal substrate made of various materials.

(39) The semiconductor structure **120** may be disposed on the substrate **170**. The semiconductor structure **120** may include a first conductivity-type semiconductor layer **121**, a second conductivity-type semiconductor layer **122**, and an active layer **123** disposed between the first conductivity-type semiconductor layer **121** and the second conductivity-type semiconductor layer

122. In the drawing, the first conductivity-type semiconductor layer **121** is illustrated as facing upward and the second conductivity-type semiconductor layer **122** is illustrated as facing the substrate **170**, but the present invention is not limited thereto.

(40) The first conductivity-type semiconductor layer **121** may be implemented using at least one selected from among a III-V group compound semiconductor, a II-VI group compound semiconductor, and the like. The first conductivity-type semiconductor layer **121** may be made of a semiconductor material having an empirical formula of $\text{In}_{0.5x}\text{Al}_{0.5y}\text{Ga}_{0.5(1-x-y)}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, and $0 \leq x+y \leq 1$) or may be made of a material selected from among AlInN, AlGaAs, GaP, GaAs, GaAsP, and AlGaInP. The first conductivity-type semiconductor layer **121** may be doped with a first dopant. The first dopant may be an n-type dopant such as silicon (Si), germanium (Ge), tin (Sn), selenium (Se), or tellurium (Te). That is, the first conductivity-type semiconductor layer **121** may be an n-type semiconductor layer doped with an n-type dopant.

(41) Meanwhile, an uneven structure may be formed on the first conductivity-type semiconductor layer **121**. The uneven structure can improve light extraction efficiency of the semiconductor structure **120**.

(42) The second conductivity-type semiconductor layer **122** may be implemented using at least one selected from among a III-V group compound semiconductor, a II-VI group compound semiconductor, and the like. The second conductivity-type semiconductor layer **122** may be made of a semiconductor material having an empirical formula of $\text{In}_{0.5x}\text{Al}_{0.5y}\text{Ga}_{0.5(1-x-y)}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$, and $0 \leq x+y \leq 1$) or may be made of a material selected from among AlInN, AlGaAs, GaP, GaAs, GaAsP, and AlGaInP. The second conductivity-type semiconductor layer **122** may be doped with a second dopant. The second dopant may be a p-type dopant such as magnesium (Mg), zinc (Zn), calcium (Ca), strontium (Sr), or barium (Ba). That is, the second conductivity-type semiconductor layer **122** may be a p-type semiconductor layer doped with a p-type dopant.

(43) The active layer **123** may be disposed between the first conductivity-type semiconductor layer **121** and the second conductivity-type semiconductor layer **122**. The active layer **123** is a layer in which electrons (or holes) injected through the first conductivity-type semiconductor layer **121** meet holes (or electrons) injected through the second conductivity-type semiconductor layer **122**. As electrons and holes are recombined to transition to a low energy level, the active layer **123** may generate light having a wavelength corresponding thereto.

(44) The active layer **123** may have any one of a single well structure, a multi well structure, a single quantum well structure, a multi quantum well (MQW) structure, a quantum dot structure, and a quantum line structure, but the present invention is not limited thereto. When the active layer **123** is formed in a well structure, a well layer/barrier layer of the active layer **123** may be formed to include at least one pair structure selected from among InGaN/GaN, InGaN/InGaN, GaN/AlGaIn, InAlGaIn/GaN, GaAs(InGaAs)/AlGaAs, and GaP(InGaP)/AlGaP, but the present invention is not limited thereto. The well layer may include a material having a narrower band gap than the barrier layer.

(45) The bonding layer **171** may bond the substrate **170** and the semiconductor structure **120**. In other words, the semiconductor structure **120** and structures positioned below the semiconductor structure **120** may be disposed on the substrate **170** by the bonding layer **171**. The bonding layer **171** may be made of at least one selected from among AuSn, NiSn, AuIn, CuSn, SiO_2 , and a resin, but the present invention is not limited thereto. For example, the bonding layer **171** may include a barrier metal or a bonding metal and may include, for example, at least one selected from among titanium (Ti), gold (Au), tin (Sn), nickel (Ni), chromium (Cr), gallium (Ga), indium (In), bismuth (Bi), copper (Cu), silver (Ag), and tantalum (Ta).

(46) Meanwhile, the semiconductor structure **120** may include a first recess R1 having a predetermined depth. Specifically, the first recess R1 may be formed through mesa etching so as to pass through the second conductivity-type semiconductor layer **122** and the active layer **123** and extend to a partial region of the first conductivity-type semiconductor layer **121**. Accordingly, a

portion of the first conductivity-type semiconductor layer **121** may be exposed. Therefore, the first electrode **141** and the first interconnection line **151** may be electrically connected to the first conductivity-type semiconductor layer **121** through the first recess **R1**.

(47) The channel layer **130** may be disposed in a partial region of a lower portion of the semiconductor structure **120**. In addition, the channel layer **130** may be disposed to surround an edge of a lower portion of each semiconductor structure **120**. The channel layer **130** may be partially disposed below the first recess **R1**. In addition, the channel layer **130** may be disposed between the substrate **170** and the semiconductor structure **120**.

(48) Specifically, the channel layer **130** may cover the first recess **R1**, and a side surface of the active layer **123**, a portion of the first conductivity-type semiconductor layer **121**, and a portion of the second conductivity-type semiconductor layer **122**, which are exposed by the first recess **R1**.

(49) The channel layer **130** may be disposed such that a side surface of the first conductivity-type semiconductor layer **121** is exposed in the first recess **R1**. That is, the channel layer **130** may be disposed to be in contact with the side surface of the first conductivity-type semiconductor layer **121**, and a lower surface of the first conductivity-type semiconductor layer **121** may be exposed. Similarly, the channel layer **130** may be disposed such that a portion of the second conductivity-type semiconductor layer **122** is exposed. For example, a side surface of the second conductivity-type semiconductor layer **122** may be exposed. In addition, the channel layer **130** may be disposed between adjacent semiconductor structures **120**, between the first pads **181** connected to the semiconductor structures **120**, and between the second pads **182** connected to the semiconductor structures **120**. Thus, the channel layer **130** may cover a portion of the second conductivity-type semiconductor layer **122**. For example, the channel layer **130** may expose a portion of the second conductivity-type semiconductor layer **122** through a first hole **H1**.

(50) The channel layer **130** may be made of an insulating material. Specifically, the channel layer **130** may be made of a non-conductive oxide or nitride. For example, the channel layer **130** may be formed as one selected from among a silicon oxide (SiO_2) layer, a silicon nitride (Si_3N_4) layer, a titanium oxide (TiO_x), and an aluminum oxide (Al_2O_3) layer, but the present invention is not limited thereto.

(51) The channel layer **130** may allow the semiconductor structure **120** to be electrically connected only through the first interconnection line **151** and the second interconnection line **152** and provide structural insulation between adjacent semiconductor structures **120**. In addition, the channel layer **130** may protect the second electrode **142**, the first insulating layer **161**, the second insulating layer **162**, the bonding layer **171**, and the substrate **170**, which are disposed below the channel layer **130** and the semiconductor structure **120**, from external contaminants or the like. As a result, a supporting force for the semiconductor structure **120** can be improved, and thus, the channel layer **130** can protect the semiconductor structure **120** from damage that may occur in a manufacturing process.

(52) The first electrode **141** may be disposed in the first recess **R1** so as to be electrically connected to the first conductivity-type semiconductor layer **121**. The second electrode **142** may be disposed below the second conductivity-type semiconductor layer **122** to be electrically connected to the second conductivity-type semiconductor layer **122**.

(53) Specifically, the first electrode **141** may be disposed in the first recess **R1**. The first electrode **141** may be disposed in a region exposed by the channel layer **130** in the first recess **R1**.

(54) The second electrode **142** may be disposed on the second conductivity-type semiconductor layer **122** exposed by the channel layer **130** in the first hole **H1**.

(55) The first electrode **141** and the second electrode **142** may be made of a material having electrical conductivity. In addition, the first electrode **141** and the second electrode **142** may be made of a material having high reflectivity. For example, the first electrode **141** and the second electrode **142** may be made of at least one selected from among Ti, ruthenium (Ru), rhodium (Rh), iridium (Ir), Mg, Zn, aluminum (Al), indium (In), Ta, palladium (Pd), cobalt (Co), Ni, Si,

germanium (Ge), Ag, platinum (Pt), and Au, or an alloy thereof. Furthermore, the first electrode **141** and the second electrode **142** may be ohmic electrodes and may be made, for example, of at least one selected from among indium tin oxide (ITO), indium zinc oxide (IZO), indium zinc tin oxide (IZTO), indium aluminum zinc oxide (IAZO), indium gallium zinc oxide (IGZO), indium gallium tin oxide (IGTO), aluminum zinc oxide (AZO), antimony tin oxide (ATO), gallium zinc oxide (GZO), IZO nitride (IZON), Al—Ga ZnO (AGZO), In—Ga ZnO (IGZO), ZnO, IrO.sub.x, RuO.sub.x, NiO, RuO.sub.x/ITO, Ni/IrO.sub.x/Au, and Ni/IrO.sub.x/Au/ITO, but the present invention is not limited to such materials. In this case, light generated from the semiconductor structure **120** may be reflected from the first electrode **141** and the second electrode **142** and emitted upward. As a result, light extraction efficiency of the semiconductor structure can be improved. However, the present invention is not necessarily limited to such materials.

(56) In addition, various materials for an ohmic contact may be included in the first electrode **141** and the second electrode **142**.

(57) The reflective layer **143** may be disposed below the second electrode **142**. The reflective layer **143** may be made of a material having electrical conductivity. In addition, the reflective layer **143** may be made of a metal material having high reflectivity. The reflective layer **143** may be made of a metal or an alloy including at least one selected from among Ag, Ni, Al, Rh, Pd, Ir, Ru, Mg, Zn, Pt, Cu, Au, and hafnium (Hf). In addition, the reflective layer **143** may be made of the metal or alloy. For example, the reflective layer **143** may include at least one selected from among Ag, Al, a Ag—Pd—Cu alloy, and a Ag—Cu alloy, but the present invention is not limited to such materials.

(58) The first insulating layer **161** may protect components of the semiconductor device package **100A** and may electrically insulate adjacent components from each other. In addition, as the first insulating layer **161**, an insulating layer having high transmittance may be used. For example, the first insulating layer **161** may be made of at least one selected from among SiO.sub.2, Si.sub.xO.sub.y, Si.sub.3N.sub.4, Si.sub.xN.sub.y, SiO.sub.xN.sub.y, TiO.sub.2, ZrO.sub.2, Si.sub.3N.sub.4, Al.sub.2O.sub.3, AlN, and MgF.sub.2, but the present invention is not limited to such materials.

(59) In addition, the first insulating layer **161** may have a distributed Bragg reflector (DBR) structure. For example, the first insulating layer **161** may reflect light having a predetermined wavelength band, and rather than a single DBR, a multi-DBR may be applied to increase reflectance and improve luminous flux. In addition, the first insulating layer **161** may include a plurality of layers having different refractive indices.

(60) The first insulating layer **161** may cover a portion of the first electrode **141** to expose a partial region of the first electrode **141**. The first insulating layer **161** may be disposed below the second electrode **142**, the channel layer **130**, and the second interconnection line **152** to cover the second electrode **142** and the channel layer **130**. Due to such a configuration, the first insulating layer **161** may provide electrical insulation between the first interconnection line **151** and the second interconnection line **152**.

(61) The second insulating layer **162** may be disposed below the first insulating layer **161** and the first interconnection line **151**. The second insulating layer **162** may cover the first interconnection line **151** and the first insulating layer **161**. Due to such a configuration, the second insulating layer **162** may electrically insulate the first interconnection line **151** from the outside and protect the first interconnection line **151** from contaminants. As a result, the second insulating layer **162** can improve reliability of the semiconductor device package.

(62) The passivation layer **163** may be disposed on an upper portion of the semiconductor device package. That is, the passivation layer **163** may be disposed on the semiconductor structure **120** and, specifically, the first conductivity-type semiconductor layer **121**. In addition, when the first conductivity-type semiconductor layer **121** has an uneven structure, the passivation layer **163** disposed on the first conductivity-type semiconductor layer **121** may have an uneven structure like the first conductivity-type semiconductor layer **121**. However, the present invention is not limited

thereto, and as will be described below, the passivation layer **163** may be partially disposed on the semiconductor structure **120**.

(63) The passivation layer **163** may be disposed on an upper surface of the semiconductor device package **100A**, but the present invention is not limited thereto. For example, a portion of the first pad **181** and a portion of the second pad **182** may be disposed at a higher level than the passivation layer **163** through a second-first hole H2-1 and a second-second hole H2-2, respectively.

(64) The first interconnection line **151** may be electrically connected to the first electrode **141**. The second interconnection line **152** may be electrically connected to the second electrode **142**.

(65) The first interconnection line **151** may be electrically connected to the first electrode **141** and may extend to one side of the semiconductor structure **120** to be connected to the first pad **181**.

(66) In addition, the second interconnection line **152** may be electrically connected to the second electrode **142** and may extend to the other side of the semiconductor structure **120** to be electrically connected to the second pad **182**.

(67) The first interconnection line **151** and the second interconnection line **152** may extend in different directions on the substrate **170**. For example, extending directions of the first interconnection line **151** and the second interconnection line **152** may be perpendicular to each other. This will be described in detail below with reference to FIG. 2.

(68) Specifically, the second interconnection line **152** may be disposed between the semiconductor structure **120** and the substrate **170**. In addition, the second interconnection line **152** may be disposed on the second electrode **142** and electrically connected to the second electrode **142**. The second interconnection line **152** may extend from the second electrode **142** in a direction toward an outer side surface of the semiconductor structure **120**. For example, the second interconnection line **152** may include a second end portion **152c** that extends to protrude further than the outer side surface of the semiconductor structure **120**. In other words, one end portion of the second interconnection line **152** may be connected to the second electrode **142**. The second end portion **152c** of the second interconnection line **152** may extend from one end portion of the second interconnection line **152** toward the edge of the substrate **170**. Accordingly, the second end portion **152c** may be electrically connected to the second pad **182** which will be described below. In this case, the second end portion **152c** may be disposed to protrude further than the side surface of the semiconductor structure **120** below the semiconductor structure **120**. Due to such a configuration, the second interconnection line **152** may be easily connected to the second pad **182** disposed at a side portion of the semiconductor structure **120**.

(69) That is, as shown in FIG. 2 below, the second end portion **152c** of the second interconnection line **152** may be disposed to protrude further toward the edge of the substrate **170** than an edge of the semiconductor structure **120**. That is, the edge of the semiconductor structure **120** may be etched, and thus, the semiconductor structure **120** may be disposed only at a central portion of the substrate (crossing region of regions A and B, regions C and D, and regions E and F). Accordingly, the semiconductor structure **120** may expose the second end portion **152c** disposed at the edge of the substrate. The second pad **182** may pass through the channel layer **130** to be electrically connected to the second pad **182**. Therefore, the second end portion **152c** of the second interconnection line **152** and the second pad **182** may overlap each other in a thickness direction (z-axis direction) of the substrate **170** at the edge of the substrate **170**.

(70) The first interconnection line **151** may be disposed on the first electrode **141** between the semiconductor structure **120** and the substrate **170**. In addition, the first interconnection line **151** may extend from the first electrode **141** in a direction toward the edge of the semiconductor structure **120**.

(71) The first interconnection line **151** may include a first through-portion **151a**, a first connection portion **151b**, and a first end portion **151c**. The first interconnection line **151** may be spaced apart and insulated from the second interconnection line **152** by the first insulating layer **161**.

(72) The first through-portion **151a** may pass through the active layer **123**, the second conductivity-

type semiconductor layer **122**, and the first insulating layer **161**. In addition, the first through-portion **151a** may pass through a portion of the first conductivity-type semiconductor layer **121**.

(73) One end of the first through-portion **151a** may be connected to the first electrode **141**. The first through-portion **151a** may extend from the first electrode **141** toward the substrate **170**. The other end of the first through-portion **151a** may be connected to one end of the first connection portion **151b**.

(74) The first connection portion **151b** may extend from one end thereof toward the edge of the substrate **170** along one surface of the first insulating layer **161**. The other end of the first connection portion **151b** may be connected to one end of the first end portion **151c**.

(75) The first end portion **151c** may protrude further than the outer side surface of the semiconductor structure **120**. That is, the first end portion **151c** may extend toward the edge of the substrate **170**. Accordingly, a portion of the first end portion **151c** may overlap an edge P1 of the substrate **170** in a thickness direction thereof. Therefore, the first interconnection line **151** may be easily connected to the first pad **181** disposed at the side portion of the semiconductor structure **120**.

(76) That is, as shown in FIG. 2 to be described below, the first end portion **151c** of the first interconnection line **151** may be disposed to protrude further toward the edge of the substrate **170** than the edge of the semiconductor structure **120**. Accordingly, the first end portion **151c** of the first interconnection line **151**, the channel layer **130**, and the first pad **181** may overlap each other at the edge of the substrate **170** in a direction perpendicular to the substrate **170**.

(77) The first pad **181** and the second pad **182** may be disposed to be spaced apart from the semiconductor structure **120** on the substrate **170**. Specifically, the first pad **181** and the second pad **182** may be disposed to surround the semiconductor structure **120** at the side portion of the semiconductor structure **120** or the edge of the substrate **170**.

(78) The first pad **181** may be electrically connected to the first conductivity-type semiconductor layer **121** through the first interconnection line **151** and the first electrode **141**. The second pad **182** may be electrically connected to the second conductivity-type semiconductor layer **122** through the second interconnection line **152** and the second electrode **142**.

(79) The first pad **181** may include a first region **181a** and a second region **181b**.

(80) First, one end of the first region **181a** may be connected to the other end of the first end portion **151c**. The first region **181a** may pass through the first insulating layer **161**, the channel layer **130**, and the passivation layer **163**.

(81) The second region **181b** may be disposed to protrude from the passivation layer **163**. The first pad **181** may be disposed to be spaced apart from the semiconductor structure **120**. In particular, the first pad **181** may be disposed to be spaced apart from the side surface of the semiconductor structure **120** and the passivation layer **163** covering the side surface, but the present invention is not limited thereto.

(82) The second pad **182** may include a first region **182a** and a second region **182b**.

(83) First, the first region **182a** may pass through the channel layer **130** and the passivation layer **163**. One end of the first region **181a** may be connected to the other end of the second end portion **152c** of the second interconnection line **152**.

(84) One end of the second region **182a** may be connected to the other end of the second end portion **152c**. The second region **182b** may be disposed to protrude from the passivation layer **163**. The second pad **182** may be disposed to be spaced apart from the semiconductor structure **120**. In particular, the second pad **182** may be disposed to be spaced apart from the side surface of the semiconductor structure **120** and the passivation layer **163** covering the side surface.

(85) FIG. 2 is a plan view of the semiconductor device package according to the first embodiment. FIG. 3 is a cross-sectional view taken along line M-M' in FIG. 2. FIG. 4 is an enlarged view of region K in FIG. 3. FIG. 5 is an enlarged view of region L in FIG. 3. FIG. 6 is a graph showing a contrast ratio according to a maximum height of the side surface of the semiconductor structure.

FIG. 7 is a graph showing a contrast ratio according to a separation distance between adjacent semiconductor structures. FIG. 8 is a view illustrating the first interconnection line in FIG. 2. FIG. 9 is a view illustrating the second interconnection line in FIG. 2.

(86) Referring to FIG. 2, the semiconductor device package **100A** according to the first embodiment may include the plurality of semiconductor structures **120** disposed on one substrate **170**.

(87) Specifically, the semiconductor device package **100A** may include the plurality of semiconductor structures **120** (see FIG. 1), a plurality of first interconnection lines **151-n**, a plurality of second interconnection lines **152-n**, a plurality of first pads **181-n**, and a plurality of second pads **182-n** on the substrate **170**.

(88) In FIG. 1, it has been described that one semiconductor structure **120**, one first interconnection line **151**, one second interconnection line **152**, one first pad **181**, and one second pad **182** are illustrated for convenience of description.

(89) Specifically, the plurality of first pads **181-n** and the plurality of second pads **182-n** may be disposed to be spaced apart from the plurality of semiconductor structures **120**. The plurality of first pads **181-n** and the plurality of second pads **182-n** may be disposed at the edge of the substrate **170** to surround the plurality of semiconductor structures **120**.

(90) The first interconnection lines **151-n** may be disposed between the semiconductor structures **120** and the plurality of first pads **181-n** to electrically connect first conductivity-type semiconductor layers of the semiconductor structures **120** and the plurality of first pads **181-n**.

(91) Similarly, the second interconnection lines **152-n** may be disposed between the semiconductor structures **120** and the plurality of second pads **182-n** to electrically connect second conductivity-type semiconductor layers of the semiconductor structures **120** and the plurality of second pads **182-n**.

(92) The first pads **181-n** may be disposed at upper and lower portions of the edge of the substrate **170** to face each other. The second pads **182-n** may be disposed on left and right portions of the edge of the substrate **170** to face each other. However, in some cases, the position and arrangement structure of the first pads **181-n** and the second pads **182-n** may be changed.

(93) First, the substrate **170** may be divided into central portions A, B, C, and D and the edge P1. For example, the central portions A, B, C, and D may be central regions of the substrate in which the semiconductor structures are disposed. In addition, the first interconnection lines **151-n** and the second interconnection lines **152-n** are disposed at the central portions A, B, C, and D and may be electrically connected to the plurality of semiconductor structures.

(94) The edge P1 may be a region excluding the central portions A, B, C, and D, and the plurality of first pads **181-n** and the plurality of second pads **182-n** may be disposed thereat. In addition, the first interconnection lines **151-n** and the second interconnection lines **152-n** may be partially disposed at the edge P1.

(95) Accordingly, the first interconnection line **151-n** and the second interconnection line **152-n** may be electrically connected to the first pad **181-n** and the second pad **182-n** at the edge P1, respectively and may include regions that overlap each other in a thickness direction thereof.

(96) The plurality of semiconductor structures may be disposed to be spaced apart from each other by a predetermined distance at the central portion of the substrate **170** and may emit light. Here, 16 semiconductor structures **120** are illustrated as being disposed in each of horizontal and vertical directions, but the present invention is not limited thereto. Each semiconductor structure may have a size of 500 μm ×500 μm or less. That is, each of a width and a length of the semiconductor structure may be 500 μm or less. For example, the size of the semiconductor structure may be 300 μm ×300 μm , 250 μm ×250 μm , or 110 μm ×110 μm . More preferably, each of the width and the length of the individual semiconductor structure may be in a range of 70 μm to 80 μm . However, the present invention is not limited thereto.

(97) In the plurality of semiconductor structures, lines 1 to 8 are defined as region A and lines 9 to

16 are defined as region B from the top of the substrate **170**. In addition, in the plurality of semiconductor structures, lines 1 to 8 are defined as region C and lines 9 to 16 are defined as region D from the left of the substrate **170**.

(98) Specifically, referring to FIG. 3, as described above, the second end portion **152c** may protrude further outward than an extension line of the side surface of the semiconductor structure **120**. The second end portion **152c** may be electrically connected to the second pad **182-n**.

(99) Meanwhile, the first interconnection lines **151-n** and the second interconnection lines **152-n** may be electrically connected to the plurality of semiconductor structures **120**. Although only two semiconductor structures **120** are illustrated in the drawings, substantially, as shown in FIG. 2, the plurality of semiconductor structures **120** may be disposed.

(100) A first connection portion **151b** of the first interconnection line **151-n** may be disposed along one surface of the first insulating layer **161** between the substrate **170** and the plurality of semiconductor structures **120**. A first through-portion **151a** may extend from each semiconductor structure **120** to electrically connect the plurality of semiconductor structures **120** and one first connection portion **151b**.

(101) Meanwhile, four first interconnection lines **151-n** may be disposed below one semiconductor structure **120** disposed at an outermost side.

(102) In addition, one second interconnection line **152-n** may be disposed along one surfaces of the plurality of second electrodes **142** between the substrate **170** and the plurality of semiconductor structures **120**.

(103) First, referring to FIG. 2, the plurality of first interconnection lines **151-n** ($n \geq 1$) may be disposed at the edge P1 of the substrate **170**. In this case, one first- n .sup.th interconnection line **151-n** may be electrically connected to eight semiconductor structures **120**. Accordingly, 64 first interconnection lines **151-n** may be disposed on each of upper and lower sides of the substrate **170**. That is, four first- n .sup.th interconnection lines **151-n** may be disposed below one semiconductor structure **120**. However, this is merely an example for describing the present invention, and the present invention is not limited thereto. That is, the number of the semiconductor structures **120** connected to one first- n .sup.th interconnection line **151-n** and the number of the first- n .sup.th interconnection lines **151-n** disposed below one semiconductor structure **120** may be changed. Hereinafter, for convenience of description, the first- n .sup.th interconnection lines **151-n** connected to the semiconductor structures **120** of region A are defined as a first-first interconnection line **151-1**, a first-second interconnection line **151-2**, . . . and a first-32.sup.th interconnection line **151-32** in order from the left.

(104) For example, the first-first interconnection line **151-1** may be electrically connected to eight semiconductor structures **120** disposed in a first column at a left side of region A. Here, a column is defined as a vertical line in a first direction (y-axis direction) in the substrate **170**, and a row is defined as a horizontal line in a second direction (x-axis direction) in the substrate **170**. In addition, the first direction and the second direction are defined as directions perpendicular to a third direction (z-axis direction) which is a thickness direction of the semiconductor structure.

(105) In this regard, referring to FIGS. 8 and 9, the first-first interconnection line **151-1** may include a first-1a interconnection line **151-1a**, a first-1b interconnection line **151-1b**, a first-1c interconnection line **151-1c**, and a first-1d interconnection line **151-1d**.

(106) In addition, the first-first interconnection line **151-1** may be electrically connected to the eight semiconductor structures disposed in the first column at the left side of region A. Similarly, the first-second interconnection line **151-2** may be electrically connected to eight semiconductor structures disposed in a second column at the left side of region A, and the same may be applied up to the first-32.sup.th interconnection line **151-32**. On the other hand, the 1-17.sup.th to first-32.sup.th interconnection lines **151-17** to **151-32** may be electrically connected to semiconductor structures of region C and region D.

(107) The plurality of second interconnection lines **152-n** ($n \geq 1$) may be disposed at left and right

sides of the edge P1 of the substrate **170**. In this case, one second-n.sup.th interconnection line **152-n** may be electrically connected to eight semiconductor structures.

(108) 16 second-n.sup.th interconnection lines **152-n** may be disposed at each of left and right sides of the substrate **170**. That is, unlike the first-n.sup.th interconnection line **151-n**, one second-n.sup.th interconnection line **152-n** may be disposed below one semiconductor structure **120**.

However, this is merely an example for describing the present invention, and the present invention is not limited thereto. That is, the number of the semiconductor structures connected to one second-n.sup.th interconnection line **152-n** and the number of the second-n.sup.th interconnection lines **152-n** disposed below one semiconductor structure may be changed.

(109) Hereinafter, for convenience of description, the second interconnection lines **152-n** disposed at the left side of the substrate **170** are defined as a second-first interconnection line **152-1**, a second-second interconnection line **152-2**, . . . and a 2-16.sup.th interconnection line **152-16** in order from the top. Similarly, the second interconnection lines **152-n** disposed at the right side of the substrate **170** may include 2-17.sup.th to 2-32.sup.th interconnection lines **152-17** to **152-32** in order from the top.

(110) The second-first interconnection line **152-1** may be electrically connected to eight semiconductor structures disposed in a first row of an upper side of region C. Specifically, the second-first interconnection line **152-1** may be electrically connected to second conductivity-type semiconductor layers of the eight semiconductor structures disposed in the first row of the upper side.

(111) Similarly, the second-second interconnection line **152-2** may be electrically connected to eight semiconductor structures disposed in a second row of the upper side of region C. The same may be applied up to the 2-16.sup.th interconnection line **152-16**.

(112) In addition, the same may be applied to region D. That is, the second-n.sup.th interconnection lines **152-n** may be electrically connected to eight semiconductor structures. For example, one second-n.sup.th interconnection line **152-n** may be electrically connected to eight semiconductor structures in each row of region D in order from the top of the substrate **170**.

(113) As described above, the first-n.sup.th interconnection lines **151-n** may each be electrically connected to eight semiconductor structures in region A and region B (or region C and region D) in order from the left.

(114) In addition, the second-n.sup.th interconnection lines **152-n** may each be electrically connected to eight semiconductor structures in region C and region D in order from the top.

(115) The plurality of first pads **181-n** ($n \geq 1$) may be disposed at the upper and lower sides of the edge P1 of the substrate **170**. In this case, four first-n.sup.th pads **181-n** may be disposed on the first interconnection line **151-n**. That is, a total of 128 first-n.sup.th pads **181-n** may be disposed with respect to 32 first interconnection lines **151-n**.

(116) For example, a first-first pad **181-1** may include a first-1a pad **181-1a**, a first-1b pad **181-1b**, a first-1c pad **181-1c**, and a first-1d pad **181-1d** which are disposed in order from the left at the upper side of the substrate **170**. The first-1a pad **181-1a**, the first-1b pad **181-1b**, the first-1c pad **181-1c**, and the first-1d pad **181-1d** may be electrically connected to the first-1a interconnection line **151-1a**, the first-1b interconnection line **151-1b**, the first-1c interconnection line **151-1c**, and the first-1d interconnection line **151-1d**, respectively.

(117) The first-1a interconnection line **151-1a**, the first-1b interconnection line **151-1b**, the first-1c interconnection line **151-1c**, and the first-1d interconnection line **151-1d** may be connected to first conductivity-type semiconductor layers of two adjacent semiconductor structures of the eight semiconductor structures.

(118) In addition, the plurality of first-n.sup.th pads **181-n** may be defined as a first-first pad **181-1**, a first-second pad **181-2**, . . . and a first-16.sup.th pad **181-16** in order from the left at the upper side of the substrate. The plurality of first-n.sup.th pads **181-n** may be defined as first-17.sup.th to first-32.sup.th pads **181-17** to **181-32** in order from the left at the lower side of the substrate.

(119) Accordingly, the first-first to first-16.sup.th pads **181-1** to **181-16** may be electrically connected to the first-first to first-16.sup.th interconnection lines **151-1** to **151-16** disposed in region A.

(120) The first-17.sup.th to first-32.sup.th pads **181-17** to **181-32** may be electrically connected to the first-17.sup.th to first-32.sup.th interconnection lines **151-17** to **151-32** disposed in region B.

(121) The plurality of second pads **182-n** ($n \geq 1$) may be disposed at the edge P1 of the substrate **170**. In this case, second-n.sup.th pads **182-n** may be disposed on second-n.sup.th interconnection lines **152-n**, respectively. In addition, as described above, 16 second-n.sup.th pads **182-n** may be disposed at each of the left and right sides of the substrate **170**. Furthermore, one second-n.sup.th pad **182-n** may be electrically connected to eight semiconductor structures in the same row. However, this is merely an example for describing the present invention, and the present invention is not limited thereto.

(122) First, the second-n.sup.th pads **182-n** disposed at the left side of the substrate **170** may be defined as a second-first pad **182-1**, a second-second pad **182-2**, . . . and a second-16.sup.th pad **182-16** in order from the top.

(123) Here, the second-first pad **182-1** may be disposed on the second-first interconnection line **152-1** and may be electrically connected. The second-first pad **182-1** may be electrically connected to eight semiconductor structures disposed in the first row of the upper side of region C. The same may be applied up to the second-16.sup.th pad **182-16**. In addition, the same may be applied to the second pads **182-17** to **182-32** disposed at the right side of the substrate **170**.

(124) Referring to FIG. 2 again, a fluorescent layer **190** may be disposed on the plurality of semiconductor structures **120** and the passivation layer **163** to cover the plurality of semiconductor structures **120** (although not shown in FIG. 3, the fluorescent layer **190** may be disposed on the passivation layer **163**). Accordingly, the fluorescent layer **190** may absorb light emitted from the plurality of semiconductor structures **120** and convert the absorbed light into light in a different wavelength range to emit the converted light. For example, the fluorescent layer **190** may emit white light.

(125) As described above, the plurality of first and second pads **181-n** and **182-n** may be disposed along the edge P1 of the substrate **170**. In addition, the plurality of semiconductor structures may be disposed inside the plurality of pads **181-n** and **182-n**. That is, the plurality of first and second pads **181-n** and **182-n** may be disposed to surround the plurality of semiconductor structures. In addition, the plurality of first interconnection lines **151-n** and second interconnection lines **152-n** may extend from the first and second conductivity-type semiconductor layers **121** and **122** or the first and second electrodes **141** and **142** to the edge of the substrate and be connected to the plurality of pads **181-n** and **182-n**. The plurality of semiconductor structures may not be individually formed and may be formed by growing the first to second conductivity-type semiconductor layers **121** and **122** and the active layer **123** all at once and isolating the first to second conductivity-type semiconductor layers **121** and **122** and the active layer **123** in a unit of one chip (device) through etching. Therefore, processability can be improved, and concurrently, an emission region can be increased.

(126) Referring to FIG. 3, in the semiconductor device package according to the embodiment, as described above, the plurality of semiconductor structures may be disposed to be spaced apart from each other. Hereinafter, descriptions will be given based on a first semiconductor structure **120-1** and a second semiconductor structure **120-2** which are disposed adjacent to each other.

(127) The first-first interconnection line **151-1** and the first-second interconnection line **151-2** may be disposed below the first semiconductor structure **120-1** and the second semiconductor structure **120-2**, and the first semiconductor structure **120-1** and the second semiconductor structure **120-2** may be electrically connected to the first-first interconnection line **151-1** and the first-second interconnection line **151-2**.

(128) Specifically, in the first semiconductor structure **120-1**, a first conductivity-type

semiconductor layer **121** may be electrically connected to the first-1c interconnection line **151-1c**, and in the second semiconductor structure **120-1**, a first conductivity-type semiconductor layer **121** may be electrically connected to the first-2c interconnection line **151-2c**. However, as described above, the connection between the semiconductor structure and the interconnection line may be changed according to the position of the semiconductor structure in the semiconductor device package.

(129) The first semiconductor structure **120-1** and the second semiconductor structure **120-2** may each include an outermost surface. Hereinafter, descriptions will be given based on the first semiconductor structure **120-1** and FIG. 4.

(130) The first conductivity-type semiconductor layer **121** may have a maximum height $h2$ of several micrometers or less and thus may provide a plurality of light beams through an outermost surface **121a** of the first conductivity-type semiconductor layer due to having such a minute height. Here, the maximum height may be a length between an upper surface of the first conductivity-type semiconductor layer and an upper surface of the active layer (bottom surface of the first conductivity-type semiconductor layer).

(131) Referring to FIG. 5, the first semiconductor structure **120-1** may provide a plurality of light beams through an outer surface of the first conductivity-type semiconductor layer **120-1**, and thus, optical interference may occur in the second semiconductor structure **120-2** adjacent thereto. Thus, the maximum height $h1$ of the outermost surface **121a** of the first conductivity-type semiconductor layer **121** on a lower surface **121c** of the first conductivity-type semiconductor layer **121** may be controlled to adjust an amount of light emitted through a side surface of the first semiconductor structure **120-1**, and optical interference between adjacent second semiconductor structures **120-2** may be suppressed to improve a contrast ratio. In the semiconductor structure according to the embodiment, the maximum height $h1$ of the outermost surface of the first conductivity-type semiconductor layer may be in a range of $1\ \mu\text{m}$ to $3\ \mu\text{m}$. Thus, the semiconductor device package according to the embodiment can provide an improved contrast ratio.

(132) In addition, referring to FIG. 6, a degree of interference between light emitted through the outermost surface **121a** of the first conductivity-type semiconductor layer **121** in the first semiconductor structure **120-1** and light emitted from the second semiconductor structure **120-2** may be adjusted according to a minimum separation distance $W1$ between the first conductivity-type semiconductor layer **120-1** and the second semiconductor structure **120-2**.

(133) Thus, in the semiconductor device package according to the embodiment, a length ratio of the maximum height $h1$ of the side surface of the first conductivity-type semiconductor layer to the separation distance $W1$ between adjacent semiconductor structures may be in a range of 1:3 to 1:60.

(134) When the length ratio is smaller than 1:5, there may be a limitation in that, due to a decrease in separation distance between the adjacent semiconductor structures, optical interference between the semiconductor structures is increased and thus a contrast ratio is lowered. When the length ratio is greater than 1:60, there is a process limitation in controlling the maximum height of the side surface of the first conductivity-type semiconductor structure, and there is a problem in that electrical characteristics are degraded due to current crowding during current injection.

(135) Specifically, referring to FIG. 4, the outermost surface **121a** of the first conductivity-type semiconductor layer **121** may be the only surface exposed in the first semiconductor structure **120-1** when the passivation layer **163** is not present.

(136) In addition, the first conductivity-type semiconductor layer **121** may include the outermost surface **121a**, an upper surface **121b**, the lower surface **121c**, a side surface **121d**, and a bottom surface **121e**. First, in the first conductivity-type semiconductor layer **121**, the outermost surface **121a** may be a surface which is disposed on the channel layer **130** and is in contact with the passivation layer **163**. In the first conductivity-type semiconductor layer **121**, the upper surface **121b** may be a surface disposed outside in a direction from the active layer **123** to the first

conductivity-type semiconductor layer **121** and may have uneven patterns as described below. In the first conductivity-type semiconductor layer **121**, the lower surface **121c** may be a surface exposed by the channel layer **130**, may be in contact with the channel layer **130**, and may not overlap the active layer **123** in a thickness direction thereof.

(137) In addition, the side surface **121d** of the first conductivity-type semiconductor layer **121** may be a surface formed by mesa-etching the semiconductor structure **120** up to a partial region of the first conductivity-type semiconductor layer **121** and may be an inclined surface. A side surface of the second conductivity-type semiconductor layer **122** and a side surface of the active layer **123** may also be exposed by the etching and may be inclined surfaces. The exposed side surface of the second conductivity-type semiconductor layer **122**, the exposed side surface of the active layer **123**, and the exposed side surface **121d** of the first conductivity-type semiconductor layer **121** may have the same inclination angle. However, the present invention is not limited thereto, and the side surfaces may be variously modified through a process.

(138) In the first conductivity-type semiconductor layer **121**, the side surface **121d** may be a surface which is in contact with the channel layer **130**, is surrounded by the channel layer **180**, and is in contact with the upper surface of the active layer **123**. In the first conductivity-type semiconductor layer **121**, the bottom surface **121e** may be a surface which is in contact with the active layer **123** and is the same surface as the upper surface of the active layer.

(139) In the first conductivity-type semiconductor layer according to the embodiment, a maximum height h_2 of the first conductivity-type semiconductor layer **121** may be different from the maximum height of the outermost surface **121a** of the first conductivity-type semiconductor layer **121**. Due to such a configuration, an area, in which the first conductivity-type semiconductor layer and the active layer overlap in the thickness direction (z-direction), can be reduced, thereby reducing light generation through the outermost surface **121a** of the first conductivity-type semiconductor layer **121** to improve a contrast ratio.

(140) Referring to FIG. 5, a minimum separation distance W_1 between adjacent semiconductor structures **120** may be smaller than a maximum width W_2 of the semiconductor structure.

(141) According to the embodiment, a length ratio of the minimum separation distance W_1 between the adjacent semiconductor structures **120** to the maximum width W_2 of the semiconductor structure may be in a range of 1:5 to 1:20. When the length ratio is smaller than 1:5, there may be a limitation in that, due to a decrease in distance between the adjacent semiconductor structures, light emitted through an outer surface interferes with an adjacent semiconductor structure. When the length ratio is greater than 1:20, there is a problem in that, due to an increase in area of the first conductivity-type semiconductor layer, current spreading is decreased in the semiconductor structure.

(142) FIG. 10 is a sectional view of a semiconductor device package according to a second embodiment.

(143) A semiconductor device package **100B** according to the second embodiment may include the substrate **170**, the plurality of semiconductor structures **120**, the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, and the second pad **182** which have been described with reference to FIG. 1, and the above-described contents may be equally applied.

(144) However, an upper surface **121b** of a first conductivity-type semiconductor layer **121** may include a first surface **121b-1**, a second surface **121b-2** disposed below the first surface **121b-1**, and an inclined surface **121b-3** positioned between the first surface **121b-1** and the second surface **121b-2**. In addition, a plurality of first surfaces **121b-1**, a plurality of second surfaces **121b-2**, and a plurality of inclined surfaces **121b-3** may be formed, and a side surface of the first conductivity-type semiconductor layer **121** may have a plurality of inclined surfaces to have a step structure.

(145) In addition, in the first conductivity-type semiconductor layer **121**, a height **h3** from a lower surface **121c** exposed by a first recess **R1** to the first surface **121b-1** may be greater than a height **h4** from the lower surface **121c** to the second surface **121b-2** of the first conductivity-type semiconductor layer **121**.

(146) In the semiconductor device package according to the second embodiment, a height ratio of the height **h4** from the lower surface **121c** to the second surface **121b-2** of the first conductivity-type semiconductor layer **121** to the height **h3** from the lower surface **121c** exposed by the first recess **R1** to the first surface **121b-1** may be in a range of 1:1 to 1:10. Accordingly, in the semiconductor device package according to the second embodiment, an amount of light through an outer surface can be reduced to improve a contrast ratio, and a thickness of the first conductivity-type semiconductor layer can be maintained to prevent a decrease in spreading caused by current crowding.

(147) When the height ratio is smaller than 1:1, there is a problem in that luminous flux is lowered due to degradation in electrical characteristics (for example, current spreading) in each semiconductor structure. When the height ratio is greater than 1:10, there is a problem in that, due to light absorption occurring in the first-conductivity-type semiconductor layer, light extraction efficiency is lowered.

(148) In addition, a length of the second surface **121b-2** in a second direction (x-axis direction) may be in a range of 10 μm to 150 μm . Due to such a configuration, a contrast ratio and luminous flux can be maintained. When the length is smaller than 10 μm , the contrast ratio is decreased. When the length is greater than 150 μm , there is a problem in that, due to degradation in electrical characteristics caused by current crowding, the luminous flux is decreased.

(149) FIG. **11** is a cross-sectional view of a semiconductor device package according to a third embodiment. FIG. **12** is a cross-sectional view of the semiconductor device package according to the third embodiment corresponding to FIG. **3**. FIG. **13** is an enlarged view of region N in FIG. **12**. FIG. **14** is an enlarged view of region O in FIG. **12**. FIG. **15** is a graph showing a contrast ratio according to an intermediate layer.

(150) Referring to FIG. **11**, a semiconductor device package **100C** according to the third embodiment may include a substrate **170**, a plurality of semiconductor structures **120** disposed to be spaced apart from each other, and intermediate layers **164** disposed on side surfaces of the semiconductor structures **120**.

(151) In addition, the descriptions of the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, and the second pad **182**, which have been described in the semiconductor device package according to the first embodiment, may be equally applied to the semiconductor device package **100C** according to the third embodiment. Therefore, detailed descriptions thereof will be omitted. In addition, when the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, and the second pad **182** are associated with the intermediate layer **164**, which will be described below, contents described below may be applied to corresponding components.

(152) Specifically, the intermediate layer **164** may be disposed on an outer surface of a first conductivity-type semiconductor layer **121**. Specifically, the intermediate layer **164** may be in direct contact with the first conductivity-type semiconductor layer **121** and may be disposed inside the passivation layer **163** disposed on the outer surface of the first conductivity-type semiconductor layer **121** or on an outer surface of the passivation layer **163**. The specific position of the intermediate layer **164** will be described in detail with reference to FIGS. **13**, **16**, and **17** below.

(153) The intermediate layer **164** may prevent light emitted to the outer surface of the first

conductivity-type semiconductor layer **121** from being transmitted and may reflect the light, thereby preventing occurrence of optical interference with light emitted from an adjacent semiconductor structure. Accordingly, the intermediate layer **164** according to the embodiment may suppress optical interference between the plurality of semiconductor structures **120**, thereby improving a contrast ratio of the semiconductor device package.

(154) The intermediate layer **164** may be made of a material having low light transmittance. Specifically, the intermediate layer **164** may be made of any one selected from among metal, ceramic, and semiconductor materials. Preferably, the intermediate layer **164** may be made of a ceramic or semiconductor material to improve heat resistance of the semiconductor device package. For example, the intermediate layer **164** may include Si, SiC, TiN, TiO₂, or the like, but the present invention is not limited to such materials.

(155) In addition, the intermediate layer **164** may include a plurality of layers to have low light transmittance and, at the same time, to prevent permeation of external moisture and contaminants, thereby improving reliability of the semiconductor device package.

(156) In addition, light emitted to a side surface can be blocked by the intermediate layer **164**, thereby improving a contrast ratio of the semiconductor device package. Accordingly, a thickness of a fluorescent layer **190** can also be adjusted.

(157) Specifically, a length ratio of a maximum height h_1 of an outermost surface **121a** of the first conductivity-type semiconductor layer **121** to be described below to the thickness of the fluorescent layer **190** may be in a range of 1:1.1 to 1:2.3.

(158) When the length ratio is smaller than 1:1.1, there is a problem in that, due to a decrease in thickness of the fluorescent layer, light uniformity is decreased. However, when the length ratio is greater than 1:2.3, there is a problem in that emitted light moves to a fluorescent layer on an adjacent semiconductor structure, and thus crosstalk is generated.

(159) Referring to FIGS. **12** to **15**, the intermediate layer **164** may be disposed on the outermost surface **121a** of the first conductivity-type semiconductor layer **121**. Specifically, the intermediate layer **164** may be disposed between a lower surface **121c** of the first conductivity-type semiconductor layer **121** and an upper surface **121b** of the first conductivity-type semiconductor layer **121** to be in contact with the outermost surface **121a** of the first conductivity-type semiconductor layer **121**. The intermediate layer **164** may be disposed to overlap the outermost surface **121a** of the first conductivity-type semiconductor layer **121** in a first direction (y-axis direction) and a second direction (x-axis direction), thereby easily blocking light emitted to the outermost surface **121a** of the first conductivity-type semiconductor layer **121** from being transmitted. Here, as described above, the first direction (y-axis direction) and the second direction (x-axis direction) are directions perpendicular to a thickness direction (z-axis direction).

(160) In addition, in the first conductivity-type semiconductor layer, a maximum height h_2 of the first conductivity-type semiconductor layer **121** may be different from a maximum height h_1 of the outermost surface **121a** of the first conductivity-type semiconductor layer **121**. Due to such a configuration, an area, in which the first conductivity-type semiconductor layer and the active layer overlap in the thickness direction (z-direction), can be reduced, thereby reducing light generation through the outermost surface **121a** of the first conductivity-type semiconductor layer **121** to improve a contrast ratio.

(161) In addition, referring to FIG. **15**, FIG. **15** shows a contrast ratio indicating a degree of interference between light emitted through the outermost surface **121a** of the first conductivity-type semiconductor layer **121** and light emitted from the second semiconductor structure **120-2** as the maximum height h_1 of the outermost surface **121a** of the first conductivity-type semiconductor layer is controlled when an intermediate layer is present (third embodiment) and when an intermediate layer is not present (first embodiment).

(162) When the intermediate layer is not present, as the maximum height h_1 of the outermost surface **121a** of the first conductivity-type semiconductor layer is controlled, it can be seen that the

light emitted through the outermost surface **121a** of the first conductivity-type semiconductor layer **121** is decreased and thus a contrast ratio is improved. However, when the maximum height **h1** of the outermost surface **121a** of the first conductivity-type semiconductor layer is greater than or equal to a predetermined height, it can be seen that the contrast ratio is not significantly improved. (163) On the other hand, when the intermediate layer is present, it can be seen that a contrast ratio is improved and maintained regardless of the maximum height **h1** of the outermost surface **121a** of the first conductivity-type semiconductor layer. Accordingly, in the semiconductor device package according to the third embodiment, it can be seen that a contrast ratio can be improved by arranging the intermediate layer.

(164) In addition, when the intermediate layer is present and the maximum height **h1** of the outermost surface **121a** of the first conductivity-type semiconductor layer **121** is also controlled to be 3 μm or less, it can be seen that a contrast ratio is slightly improved.

(165) Furthermore, in the semiconductor device package according to the third embodiment, a length ratio of a maximum height **h1** of a side surface of the first conductivity-type semiconductor layer to a separation distance **W1** between adjacent semiconductor structures may be in a range of 1:3 to 1:60.

(166) When the length ratio is smaller than 1:5, there may be a limitation in that, due to a decrease in separation distance between the adjacent semiconductor structures, optical interference between the semiconductor structures is increased and thus a contrast ratio is lowered. When the length ratio is greater than 1:60, there is a process limitation in controlling the maximum height of the side surface of the first conductivity-type semiconductor structure, and there is a problem in that electrical characteristics are degraded due to current crowding during current injection.

(167) In addition, a width ratio of a maximum width **W3** of the outermost surface **121a** of the first conductivity-type semiconductor layer **121** to a maximum width **W2** of the semiconductor structure may be in a range of 1:10 to 1:60.

(168) When the width ratio is smaller than 1:10, there is a limitation that an amount of light emitted through the semiconductor structure is small. When the width ratio is greater than 1:60, there is a problem in that light is emitted to an upper portion of an adjacent semiconductor structure to generate crosstalk or the like.

(169) In addition, a length ratio of a thickness **dl** of the intermediate layer **164** to the maximum height **h1** of the outermost surface **121a** of the first conductivity-type semiconductor layer **121** on the lower surface **121c** of the first conductivity-type semiconductor layer **121** may be in a range of 1:11.25 to 1:30.

(170) When the length ratio is smaller than 1:11.25, there are problems in that a manufacturing process is difficult, the passivation layer and a texture structure are difficult to form, and light emitted upward is partially absorbed. When the length ratio is greater than 1:30, there may be problems in that the intermediate layer **164** may become thinner so that a process of the intermediate layer **164** is difficult, the intermediate layer **164** may not be disposed in a partial region of the outermost surface **121a** of the first conductivity-type semiconductor layer **121**, and due to an increase in light transmittance, light may be emitted through a side surface.

(171) FIG. **16** is a cross-sectional view of a semiconductor device package according to a fourth embodiment.

(172) Referring to FIG. **16**, a semiconductor device package **100D** according to the fourth embodiment may include a substrate **170**, a plurality of semiconductor structures **120** disposed to be spaced apart from each other, and intermediate layers **164** disposed on side surfaces of the semiconductor structures **120**.

(173) In addition, the descriptions of the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the first pad **181**, and the second pad **182**, which have been described in the semiconductor device

package according to the first embodiment, may be equally applied to the semiconductor device package **100D** according to the fourth embodiment. Therefore, detailed descriptions thereof will be omitted. In addition, when the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the first pad **181**, and the second pad **182** are associated with the intermediate layer **164** and a passivation layer **163** which are to be described below, contents described below may be applied to corresponding components. However, only a portion of the passivation layer **163** is illustrated as being disposed on the semiconductor structure **120**, but the present invention is not limited thereto.

(174) Specifically, the intermediate layer **164** may be disposed inside the passivation layer **163** and may be disposed to overlap an outermost surface of a first conductivity-type semiconductor layer **121** in a second direction (x-axis direction).

(175) Accordingly, the passivation layer **163** may include a plurality of layers **163a** and **163b**. For example, a first passivation layer **163a** may be disposed to be in contact with the outermost surface and a portion of an upper surface of the first conductivity-type semiconductor layer **121**. The intermediate layer **164** may be disposed to be in contact with an outermost surface of the first passivation layer **163a**, and a second passivation layer **163b** may be disposed on the intermediate layer **164**. Thus, since the second passivation layer **163b** is disposed on the intermediate layer **164** and the first insulating layer **131**, when defects are generated in the passivation layer **163b**, the intermediate layer **164** and the first passivation layer **163a** may secondarily prevent permeation of external moisture and/or other contaminants, and light emitted from an interface to a side surface of the semiconductor structure **120** may be reflected. In an example, when the first passivation layer **163a** and the second passivation layer **163b** are formed as one layer, cracks, internal defects, and the like may be easily propagated in a vertical direction. Therefore, external moisture or contaminants may be introduced into the semiconductor structure **120** through defects exposed to the outside, thereby resulting in degradation in reliability.

(176) In addition, the intermediate layer **164** may be made of a non-insulating material. For example, even when the intermediate layer **164** is a resistor, the intermediate layer **164** may be disposed inside the passivation layer **163** and may not be electrically connected to the first conductivity-type semiconductor layer **121** and thus may not affect electrical characteristics such as a current.

(177) FIG. **17** is a cross-sectional view of a semiconductor device package according to a fifth embodiment.

(178) A semiconductor device package **100E** according to the fifth embodiment may include the substrate **170**, the plurality of semiconductor structures **120**, the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, the second pad **182**, and the intermediate layer **164** which have been described with reference to FIG. **11**. Excluding the intermediate layer **164**, the above-described contents may be equally applied. However, only a portion of the passivation layer **163** is illustrated as being disposed on the semiconductor structure **120**, but the present invention is not limited thereto.

(179) Specifically, the intermediate layer **164** may be disposed on the passivation layer **163** and may be disposed to overlap an outermost surface of a first conductivity-type semiconductor layer **121** in a second direction (x-axis direction).

(180) Specifically, the passivation layer **163** may be disposed to cover the outermost surface of the first conductivity-type semiconductor layer **121** so that an outermost surface of the passivation layer **163** may have an area that is greater than that of the outermost surface of the first conductivity-type semiconductor layer **121**. In addition, since the intermediate layer **164** is disposed to cover both the outermost surface of the first conductivity-type semiconductor layer **121**

and the outermost surface of the passivation layer **163**, the intermediate layer **164** may have an area that is greater than that of the outermost surface of the first conductivity-type semiconductor layer **121** and that of the outermost surface of the passivation layer **163**.

(181) Accordingly, in the semiconductor device package **100E** according to the fifth embodiment, a maximum height of the intermediate layer **164** may be greater than a maximum height of the outermost surface of the first conductivity-type semiconductor layer **121** and a maximum height of the outermost surface of the passivation layer **163**. Due to such a configuration, in the semiconductor device package **100E** according to the fifth embodiment, the intermediate layer **164** may prevent light emitted toward an adjacent semiconductor structures from being transmitted as much as possible as compared with FIGS. **11** and **16**, thereby suppressing occurrence of optical interference between adjacent semiconductor structures. Accordingly, a contrast ratio can be improved.

(182) FIGS. **18A** to **18C** are modified examples of FIG. **11**.

(183) First, referring to FIG. **18A**, a semiconductor device package **100F** according to the modified example may include the substrate **170**, the plurality of semiconductor structures **120**, the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, the second pad **182**, and the intermediate layer **164** which have been described with reference to FIG. **11**.

Excluding the intermediate layer **164**, the above-described contents may be equally applied. However, only a portion of the passivation layer **163** is illustrated as being disposed on the semiconductor structure **120**, but the present invention is not limited thereto.

(184) The intermediate layer **164** may include a first intermediate layer **164a** and a second intermediate layer **164b**. First, as described with reference to FIG. **11**, the first intermediate layer **164a** may be disposed on an outermost surface of a first conductivity-type semiconductor layer **121** to be in contact with the outermost surface of the first conductivity-type semiconductor layer **121**. In this case, the second intermediate layer **164b** may extend from the first intermediate layer **164a** to be disposed on a portion of an upper surface of the first conductivity-type semiconductor layer **121**.

(185) Thus, in the semiconductor device package **100F** according to the modified example, the intermediate layer **164** may extend from an outermost portion to a portion of the upper surface of the first conductivity-type semiconductor layer **121** and thus may allow light to be emitted to an upper portion of the semiconductor structure **120** as much as possible rather than to a side surface of the semiconductor structure **120**. Accordingly, it is possible to further suppress occurrence of optical interference between adjacent semiconductor structures **120**.

(186) Specifically, a width ratio of a maximum width **W4** of the second intermediate layer **164b** to a maximum width **W2** of the semiconductor structure **120** may be in a range of 1:20 to 1:30.

(187) When the width ratio is smaller than 1:20, there is a problem in that, due to occurrence of optical interference between adjacent semiconductor structures, a contrast ratio is lowered. When the width ratio is greater than 1:60, there may be a problem in that the second intermediate layer **164b** absorbs light emitted upward and thus an amount of light is decreased.

(188) Accordingly, since the width ratio of the maximum width **W4** of the second intermediate layer **164b** to the maximum width **W2** of the semiconductor structure **120** may be assumed to be in a range of 1:20 to 1:30, without significantly reducing an amount of light extracted to an upper portion of the semiconductor structure, it is possible to prevent light from interfering with an upper portion of an adjacent semiconductor structure to improve a contrast ratio.

(189) In addition, the extended second intermediate layer **164b** may be equally applied to the semiconductor device package according to the fourth embodiment described with reference to FIG. **16** and the semiconductor device package according to the fifth embodiment described with reference to FIG. **17**.

(190) In addition, although not shown, a plurality of intermediate layers may be provided and may be disposed in at least two of a position between the outermost surface of the first conductivity-type semiconductor layer and the passivation layer, a position inside the passivation layer, and a position on the passivation layer. That is, in the semiconductor device packages according to the various embodiments described above, the positions, structures, and the like of the intermediate layers may be combined. For example, in the semiconductor device package, the intermediate layer may be formed in a form in which a plurality of structures of the intermediate layers described above with reference to FIGS. **11**, **16**, and **17** are reflected.

(191) Referring to FIG. **18B**, a semiconductor device package **100G** according to another modified example may include the substrate **170**, the plurality of semiconductor structures **120**, the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, the second pad **182**, and the intermediate layer **164** which have been described with reference to FIG. **11**. Excluding the intermediate layer **164**, the above-described contents may be equally applied. However, only a portion of the passivation layer **163** is illustrated as being disposed on the semiconductor structure **120**, but the present invention is not limited thereto.

(192) In addition, as described above, a first conductivity-type semiconductor layer **121** may include an outermost surface **121a**, an upper surface **121b**, a lower surface **121c**, a side surface **121d**, and a bottom surface **121e**. First, in the first conductivity-type semiconductor layer **121**, the outermost surface **121a** may be a surface which is disposed on the channel layer **130** and is in contact with the passivation layer **163**. In the first conductivity-type semiconductor layer **121**, the upper surface **121b** may be a surface disposed outside in a direction from the active layer **123** to the first conductivity-type semiconductor layer **121** and may have uneven patterns. In addition, in the first conductivity-type semiconductor layer **121**, the lower surface **121c** may be a surface exposed by the channel layer **130**, may be in contact with the channel layer **130**, and may not overlap the active layer **123** in a thickness direction thereof.

(193) In the first conductivity-type semiconductor layer **121**, the side surface **121d** may be a surface which is in contact with the channel layer **130** and is surrounded by the channel layer and may be in contact with an upper surface of the active layer **123**. In the first conductivity-type semiconductor layer **121**, the bottom surface **121e** may be a surface which is in contact with the active layer **123** and is the same surface as the upper surface of the active layer.

(194) In this case, the side surface **121d** of the first conductivity-type semiconductor layer **121** may be a surface formed by mesa-etching the semiconductor structure **120** up to a partial region of the first conductivity-type semiconductor layer **121** and may be an inclined surface. A side surface of a second conductivity-type semiconductor layer **122** and a side surface of the active layer **123** may also be exposed by the etching and may be inclined surfaces.

(195) In this case, the intermediate layer **164** may be disposed below at least one of the lower surface **121c** of the first conductivity-type semiconductor layer **121** and the side surface **121d** of the first conductivity-type semiconductor layer **121** (in FIG. **18B**, although the intermediate layer **164** is illustrated as being disposed below both the lower surface **121c** and the side surface **121d**, as described above, the intermediate layer **164** may be disposed below any one of the lower surface **121c** and the side surface **121d**).

(196) For example, a third intermediate layer **164c** may be disposed below the lower surface **121c**, and a fourth intermediate layer **164d** may be disposed below the side surface **121d**.

(197) In addition, the fourth intermediate layer **164d** may extend to be disposed on an exposed side surface of the active layer **123** and an exposed side surface of the second conductivity-type semiconductor layer **122**. Accordingly, it is possible to block light emitted to a side surface of a semiconductor structure **120-1**. Specifically, the third intermediate layer **164c** and the fourth intermediate layer **164d** may also block light which passes through the channel layer **130** and the

passivation layer **163** and is emitted to the side surface of the semiconductor structure **120**.

Accordingly, it is possible to improve a contrast ratio of the semiconductor device package **100G** according to another modified example.

(198) In addition, the third intermediate layer **164c** and the fourth intermediate layer **164d** may be disposed in at least one of a position between the channel layer **130** and the first conductivity-type semiconductor layer **121**, a position inside the channel layer **130**, and a position below the channel layer **130** (for example, between the channel layer **130** and the first insulating layer **161**).

(199) Referring to FIG. **18C**, a semiconductor device package **100H** according to still another modified example may include the substrate **170**, the plurality of semiconductor structures **120**, the bonding layer **171**, the channel layer **130**, the first electrode **141**, the second electrode **142**, the reflective layer **143**, the first interconnection line **151**, the second interconnection line **152**, the first insulating layer **161**, the second insulating layer **162**, the passivation layer **163**, the first pad **181**, the second pad **182**, and the intermediate layer **164** which have been described with reference to FIG. **1**. Excluding the intermediate layer **164**, the above-described contents may be equally applied. In addition, only a portion of the passivation layer **163** is illustrated as being disposed on the semiconductor structure **120**, but the present invention is not limited thereto.

(200) In addition, the intermediate layer **164** may further include a fifth intermediate layer **164e** disposed between adjacent semiconductor structures.

(201) Specifically, the fifth intermediate layer **164e** may extend to an adjacent semiconductor structure along an upper surface of the channel layer **130**. Thus, the intermediate layers may be connected to each other between adjacent semiconductor structures.

(202) The fifth intermediate layer **164e** may block light emitted from the semiconductor structure **120** from passing through the channel layer **130** and being emitted between adjacent semiconductor structures. Accordingly, it is possible to prevent a contrast ratio from being lowered due to optical interference between a plurality of adjacent semiconductor structures.

(203) Similarly, the fifth intermediate layer **164e** may be disposed on the channel layer **130** or inside or on the passivation layer **163** on the channel layer **130**.

(204) FIG. **19** is a conceptual view illustrating a display apparatus according to an embodiment.

(205) Referring to FIG. **19**, a display apparatus **10** according to the embodiment may include a semiconductor device package **100** including a plurality of semiconductor structures **120**, a plurality of data lines DL, a plurality of scan lines SL, a first driving unit **200**, a second driving unit **300**, and a controller **400**.

(206) The semiconductor device package **100** may include one of the semiconductor device packages **100A** to **100E** according to the first to fifth embodiments described above or one of the semiconductor device packages **100F** to **100H** according to the modified examples. As described above, the semiconductor device package **100** may include the plurality of semiconductor structures. Here, each of the plurality of semiconductor structures **120** may be one pixel PX.

(207) The plurality of data lines DL may be electrically connected to first interconnection lines connected to the plurality of semiconductor structures **120**. The connection of the plurality of data lines DL to the semiconductor structures **120** may be different according to a driving method of the display apparatus **10**. For example, the display apparatus **10** may be driven in a 2-time division manner of passive matrix driving. In this case, each of the plurality of data lines DL may be electrically connected to the first interconnection line connected to two semiconductor structures **120**. However, as described above, a connection method of the plurality of data lines DL and the first interconnection lines may be different according to the number of time divisions. For example, in a passive matrix driven in a 4-time division manner, one data line DL may be electrically connected to four semiconductor structures **120** (pixels).

(208) In addition, the plurality of data lines DL may apply currents to the semiconductor structures according to signals provided from the first driving unit **200**. A plurality of switches (not shown) may be disposed in the plurality of data lines DL, and the first driving unit **200** may provide control

signals for switching (turning on or off) the plurality of switches (not shown) to the plurality of switches (not shown). The control signal may be a pulse width modulation (PWM)-type signal. However, the present invention is not limited to such a type.

(209) In addition, the plurality of switches (not shown) may include transistors, for example, field-effect transistors (FETs). Accordingly, the first driving unit **200** may control the plurality of switches (not shown) by adjusting gate voltages applied to the plurality of switches (not shown). However, the present invention is not limited to such a type.

(210) The plurality of scan lines SL may be electrically connected to second interconnection lines connected to the plurality of semiconductor structures **120**. Similar to the data lines DL described above, the connection of the plurality of scan lines SL to the semiconductor structures **120** may be different according to a driving method of the display apparatus **10**. For example, the display apparatus **10** may be driven in a 2-time division manner of passive matrix driving. In this case, each of the plurality of scan lines SL may be electrically connected to the second interconnection line connected to two semiconductor structures **120**. However, as described above, a connection method of the plurality of scan lines SL and the second interconnection lines may be different according to the number of time divisions.

(211) Each scan line SL may be connected to two semiconductor structures **120**. In addition, the plurality of scan lines SL may apply currents to the semiconductor structures **120** according to signals provided from the second driving unit **300**. A plurality of switches (not shown) may be disposed in the plurality of scan lines SL, and the second driving unit **300** may provide control signals to the plurality of switches (not shown) for switching (turning on or off) the plurality of switches (not shown). The control signal may be a pulse width modulation (PWM)-type signal. However, the present invention is not limited to such a type.

(212) In addition, the plurality of switches (not shown) may include transistors, for example, FETs. Accordingly, the second driving unit **300** may control the plurality of switches (not shown) by adjusting gate voltages applied to the plurality of switches (not shown). However, the present invention is not limited to such a type.

(213) Specifically, the plurality of data lines DL may be electrically connected to a first conductivity-type semiconductor layer of the semiconductor structure **120** through the first interconnection lines, and the plurality of scan lines SL may be electrically connected to a second conductivity-type semiconductor layer of the semiconductor structure **120** through the second interconnection lines. Due to such a configuration, the plurality of data lines DL and the plurality of scan lines SL may inject currents into the plurality of semiconductor structures **120**, and thus, the plurality of semiconductor structures **120** may emit light.

(214) That is, the display apparatus **10** according to the embodiment may control the PWM signals provided to the data lines DL and the scan lines SL through the first driving unit **200** and the second driving unit **300**, thereby controlling light emission of the plurality of semiconductor structures **120**.

(215) The controller **400** may provide control signals to the first driving unit **200** and the second driving unit **300**. The controller **400** may determine the number of time divisions for image data input in one frame and may provide control signals corresponding to the determined number of time divisions to the first driving unit **200** and the second driving unit **300**. Due to such a configuration, the display apparatus **10** may change the number of time divisions according to image data, but the present invention is not limited thereto.

(216) FIGS. **20A** to **20M** are views illustrating a method of manufacturing a semiconductor device package according to an embodiment.

(217) Referring to FIG. **20A**, an operation of providing a temporary substrate T and forming a semiconductor structure **120** on the temporary substrate T may be performed. That is, a first conductivity-type semiconductor layer **121**, an active layer **123**, and a second conductivity-type semiconductor layer **122** may be sequentially grown on the temporary substrate T.

(218) The temporary substrate T may include a transparent, conductive, or insulating substrate. The temporary substrate T may be made of a material suitable for semiconductor material growth or may be a carrier wafer. For example, the temporary substrate T may be made of at least one selected from among sapphire (Al.sub.2O.sub.3), SiC, Si, GaAs, GaN, ZnO, Si, GaP, InP, Ge, and Ga.sub.2O.sub.3, but the present invention is not limited to such a type.

(219) The semiconductor structure **120** may include the first conductivity-type semiconductor layer **121**, the second conductivity-type semiconductor layer **122**, and the active layer **123** disposed between the first conductivity-type semiconductor layer **121** and the second conductivity-type semiconductor layer **122**. The semiconductor structure **120** may be grown through a vapor deposition method such as a metal organic chemical vapor deposition (MOCVD) method, a molecular beam epitaxy (MBE) method, or a hydride vapor phase epitaxy (HVPE) method, but the present invention is not limited thereto.

(220) Referring to FIG. **20B**, an operation of mesa-etching a portion of the semiconductor structure **120** to form a first recess R1 may be performed. The first recess R1 may be formed to have a predetermined depth from the second conductivity-type semiconductor layer **122**. The first recess R1 may be formed down to a partial region of the first conductivity-type semiconductor layer **121**. That is, portions of the second conductivity-type semiconductor layer **122**, the active layer **123**, and the first conductivity-type semiconductor layer **121** may be etched. Accordingly, a side surface and an exposed lower surface of the first conductivity-type semiconductor layer **121**, a side surface of the active layer **123**, and a side surface and an upper surface of the second conductivity-type semiconductor layer **122** may be exposed.

(221) Referring to FIG. **20C**, an operation of forming a channel layer **130** on the semiconductor structure **120** may be performed. In this case, the channel layer **130** may be formed only in a partial region of the semiconductor structure **120**. That is, the channel layer **130** may expose portions of the first conductivity-type semiconductor layer **121** and the second conductivity-type semiconductor layer **122**.

(222) Specifically, the channel layer **130** may cover a portion of the first recess R1. In addition, the channel layer **130** may cover the side surface and a portion of the upper surface of the second conductivity-type semiconductor layer **122** adjacent to the first recess R1. Furthermore, the channel layer **130** may expose a portion of the first conductivity-type semiconductor layer **121** through another hole in the first recess R1. A first electrode **141** to be described below may be disposed in the first recess R1.

(223) The channel layer **130** may expose a portion of the second conductivity-type semiconductor layer **122** through a first hole H1 to be described below. That is, the first hole H1 may be a region of the second conductivity-type semiconductor layer **122**, in which the channel layer **130** is not formed. A second electrode **142** to be described below may be disposed in the first hole H1.

(224) Meanwhile, the first hole H1 may be formed by forming the channel layer **130** on the second conductivity-type semiconductor layer **122** and then etching a partial region of the channel layer **130**. Alternatively, a region, in which the first hole H1 is to be formed, may be covered using a mask or the like, and then, the channel layer **130** may be formed only in a partial region of the second conductivity-type semiconductor layer **122**. However, the present invention is not limited to such methods.

(225) Referring to FIG. **20D**, an operation of arranging the first electrode **141** and the second electrode **142** in the hole formed in the first recess R1 and the first hole H1 may be performed. The first electrode **141** may be disposed in the first recess R1. Specifically, the first electrode **141** may pass through the channel layer **130** in the first recess R1 and be disposed in another hole. The first electrode **141** may be electrically connected to the first conductivity-type semiconductor layer **121**.

(226) The second electrode **142** may be disposed in the first hole H1. The second electrode **142** may be electrically connected to the second conductivity-type semiconductor layer **122** exposed through the first hole H1.

(227) On the other hand, in the drawing, two second electrodes **142** are illustrated as being provided to be spaced apart from each other, but the two second electrodes **142** may be substantially connected. That is, a hole is formed in the second electrode **142**, and thus, when viewed in a cross-sectional view, the two second electrodes may be illustrated as being spaced apart from each other.

(228) In addition, a reflective layer **143** may be formed on the second electrode **142**. The reflective layer **143** may be disposed to cover an upper surface of the second electrode to reflect light generated in the active layer **123** toward the first conductivity-type semiconductor layer **121**, but the present invention is not limited thereto.

(229) Referring to FIG. **20E**, an operation of arranging a second interconnection line **152** on the second electrode **142** may be performed. The second interconnection line **152** may extend in a direction toward a side surface of the temporary substrate T. For example, the second interconnection line **152** may include a second end portion **152c** extending to an upper portion of the channel layer **130** disposed at an end of the temporary substrate T.

(230) Accordingly, the second end portion **152c** may overlap the channel layer **130** in a direction perpendicular to the temporary substrate T. The second interconnection line **152** and a pad may be electrically connected by the second end portion **152c**. Therefore, the end portion of the second interconnection line **152** may be easily connected to a second pad.

(231) Referring to FIG. **20F**, an operation of arranging a first insulating layer **161** to cover the channel layer **130**, the first electrode **141**, the second electrode **142**, and the second interconnection line **152** may be performed. The second interconnection line **152** and a first interconnection line **151** to be described below may be electrically insulated by the first insulating layer **161**.

(232) Referring to FIG. **20G**, an operation of forming the first interconnection line **151** so as to pass through the first insulating layer **161** and arranging a second insulating layer **162** may be performed. Here, the first interconnection line **151** may include a first through-portion **151a**, a first connection portion **151b**, and a first end portion **151c**.

(233) The first through-portion **151a** may extend from the first electrode **141** toward one surface of the first insulating layer **161**. The first connection portion **151b** may be bent from the first through-portion **151a** and extend along one surface of the first insulating layer **161**. The first end portion **151c** may extend in a direction toward the end of the temporary substrate T. Therefore, the first end portion **151c** of the first interconnection line **151** may be easily connected to a pad, which will be described below.

(234) The first through-portion **151a** may be disposed to pass through the first insulating layer **161**, and the first connection portion **151b** may be disposed on one surface of the first insulating layer **161**. In this case, a hole is formed from one surface of the first insulating layer **161** toward the first electrode **141**, and a first region **151a** may be disposed inside the hole.

(235) In addition, the first end portion **151c** may be disposed to extend to the upper portion of the channel layer **130** disposed at the end of the temporary substrate T. That is, the first end portion **151c** may overlap the channel layer **130** in the direction perpendicular to the temporary substrate T. The first interconnection line **151** and a pad may be electrically connected by the first end portion **151c**.

(236) After the first interconnection line **151** is formed, the second insulating layer **162** may be disposed to cover the first insulating layer **161** and the first interconnection line **151**. The first interconnection line **151** may be insulated and protected by the second insulating layer **162**.

(237) Referring to FIG. **20H**, an operation of bonding a substrate **170** onto the second insulating layer **162** may be performed. In this case, a first bonding layer **171a** may be disposed on the substrate **170**, and a second bonding layer **171b** may be disposed on the second insulating layer **162**. That is, the second insulating layer **162** and the substrate **170** may be bonded by the first and second bonding layers **171a** and **171b** being bonded.

(238) Referring to FIG. **20I**, an operation of separating the temporary substrate T from the

semiconductor structure **120** may be performed. In this case, the temporary substrate T may be removed by a laser lift-off (LLO) method using an excimer laser or the like. Specifically, when light having energy greater than or equal to band gap energy of the substrate is irradiated onto the temporary substrate T, the temporary substrate T may absorb the energy to be decomposed. That is, gas molecules of a material included in the temporary substrate T may be generated to separate the temporary substrate T from the semiconductor structure **120**.

(239) Meanwhile, when the temporary substrate T is separated, the semiconductor structure **120** may be supported by the substrate **170**. In addition, heat generated in an LLO process may be effectively dissipated by the substrate **170**.

(240) Referring to FIG. **20J**, a side portion of the semiconductor structure **120** may be etched, and thus, isolation may be performed the semiconductor structure. The semiconductor structure **120** may be divided into a plurality of pieces through the isolation. Therefore, one semiconductor structure **120** may be isolated into a plurality of semiconductor structures in a chip unit. In this case, the plurality of semiconductor structures may be disposed to be spaced apart from each other by a predetermined distance.

(241) In addition, a portion of the first conductivity-type semiconductor layer **121** is etched, and thus, an outermost surface and an upper surface of the first conductivity-type semiconductor layer may be exposed.

(242) In addition, the channel layer **130** may be partially exposed. The etching may be adjusted at the channel layer **130** and the first and second end portions **151c** and **152c** of the first and second interconnection lines **151** and **152** such that the first interconnection line **151** and the second interconnection line **152** are disposed below the exposed channel layer **130**, but the present invention is not limited thereto.

(243) When the semiconductor structure **120** is etched, the channel layer **130** can protect components positioned below the channel layer **130** to minimize damage that may occur in a manufacturing process.

(244) In addition, although only one first interconnection line **151** and one second interconnection line **152** electrically connected to one first conductivity-type semiconductor layer **121** and one second conductivity-type semiconductor layer **122** are illustrated in the drawings, substantially, a plurality of first interconnection lines **151** and a plurality of second interconnection lines **152** may be provided. Furthermore, each of the first and second interconnection lines **151** and **152** may be electrically connected to the plurality of semiconductor structures **120**. That is, in FIGS. **20E** and **20G**, one first interconnection line **151** and one second interconnection line **52** are illustrated as being formed, but as described above, a plurality of first interconnection lines **151** and a plurality of second interconnection lines **152** connected to a plurality of semiconductor structures in a chip unit may actually be provided.

(245) Referring to FIG. **20K**, an operation of forming an uneven structure on the semiconductor structure **120** may be performed. Specifically, the uneven structure may be formed on the first conductivity-type semiconductor layer **121**. Light extraction efficiency of the semiconductor device package can be improved due to the uneven structure.

(246) Referring to FIG. **20L**, an operation of arranging a passivation layer **163** on the semiconductor structure **120** and the exposed channel layer **130** and forming holes H2-1 and H2-2 such that the end portions **151c** and **152c** of the interconnection lines **151** and **152** are exposed may be performed. In this case, the holes H2-1 and H2-2 may be formed through etching from an etched region S.

(247) That is, the semiconductor structure **120** may be insulated and protected by the passivation layer **163**. In this case, the passivation layer **163** may also include an uneven structure due to the uneven structure of the semiconductor structure **120**.

(248) In addition, a second-first hole H2-1 may be formed such that the first end portion **151c** is exposed, and a second-second hole H2-2 may be formed such that the second end portion **152c** is

exposed. That is, the second-first hole H2-1 may be formed by etching the channel layer **130** and the first insulating layer **161** from the passivation layer **163**. The second-second hole H2-2 may be formed by etching the channel layer **130** from the passivation layer **163**.

(249) Referring to FIG. **20M**, an operation of arranging first and second pads **181** and **182** in the etched region of the semiconductor structure **120** may be performed. In this case, the first and second pads **181** and **182** may include first regions **181a** and **182a** and second regions **181b** and **182b**.

(250) Specifically, the first regions **181a** and **182a** may be disposed in the second-first and second-second holes H2-1 and H2-2. That is, the second regions **181b** and **182b** may be disposed to protrude from the first regions **181a** and **182a** disposed in the second-first and second-second holes H2-1 and H2-2 to the etched region of the semiconductor structure **120**.

(251) The first region **181a** of the first pad **181** may be electrically connected to the first end portion **151c** of the first interconnection line **151**. The first region **181a** may pass through the first insulating layer **161**, the channel layer **130**, and the passivation layer **163**. The second region **181b** of the first pad **181** may protrude outward from the passivation layer **163** and be disposed at the side portion of the semiconductor structure **120**.

(252) The first region **182a** of the second pad **182** may be electrically connected to the second end portion **152c** of the second interconnection line **152**. The first region **182a** may pass through the channel layer **130** and the passivation layer **163**. The second region **182b** of the second pad **182** may protrude outward from the passivation layer **163** and be disposed at the side portion of the semiconductor structure **120**.

(253) Meanwhile, in the drawings, although one first pad **181** and one second pad **182** are disposed, substantially, a plurality of first pads **181** and a plurality of second pads **182** may be present as in the semiconductor structures **120** and the first and second interconnection lines **151** and **152**.

(254) As described above, in the present invention, a semiconductor structure in a large unit may be formed, and the semiconductor structure may be isolated on the substrate **170** to be separated into the semiconductor structures **120** in a chip unit. In addition, peripheral portions of the semiconductor structures corresponding to a peripheral portion of the substrate **170** may be etched together, and the first and second pads **181** and **182** may be disposed in regions in which the semiconductor structure is etched. In this case, the first and second interconnection lines **151** and **152** electrically connected to the semiconductor structure **120** may be disposed to extend to a lower portion of the etched region. Therefore, connections between the first and second pads **181** and **182** and the interconnection lines can be easily performed.

(255) That is, the plurality of semiconductor structures **120** may be disposed on one substrate **170**, and the plurality of first pads **181** and the plurality of second pads **182** may be disposed along the peripheral portion of the substrate **170**. In this case, one first pad **181** and one second pad **182** may be electrically connected to the plurality of semiconductor structures **120**. In addition, the first and second interconnection lines **151** and **152** may be formed between the semiconductor structure **120** and the substrate **170**.

(256) Accordingly, wire bonding for connecting individual chips (semiconductor devices) on a substrate and a package substrate can be omitted to miniaturize a package. In addition, processability can be improved by shortening a process. In addition, a semiconductor region can be further expanded by saving an unnecessary space.

(257) FIGS. **21A** to **21D** are views illustrating a method of manufacturing the semiconductor device package according to the third embodiment.

(258) The method of manufacturing a semiconductor device package described above with reference to FIGS. **20A** to **20I** may be equally applied to the semiconductor device package according to the third embodiment. It should be understood that FIGS. **21A** to **21D** illustrate manufacturing processes after FIG. **20I**.

(259) Referring to FIG. **21A**, an intermediate layer **164** may be disposed on an outermost surface of

a first conductivity-type semiconductor layer **121**. The intermediate layer **164** may be a thin film and may be formed through a deposition method, but the present invention is not limited to the method. The intermediate layer **164** may be disposed to overlap the outermost surface of the first conductivity-type semiconductor layer **121** in a direction (first or second direction described above) perpendicular to a thickness direction thereof. Accordingly, the intermediate layer **164** may reflect or block light emitted through the outermost surface of the first conductivity-type semiconductor layer **121** to prevent occurrence of optical interference with an adjacent semiconductor structure, thereby improving a contrast ratio.

(260) In addition, the intermediate layer **164** may be made of any one selected from among metal, ceramic, and semiconductor materials. Preferably, the intermediate layer **164** may be made of a ceramic material to improve heat resistance of the semiconductor device package. For example, the intermediate layer **164** may include Si, SiC, TiN, TiO₂, or the like, but the present invention is not limited to such materials.

(261) Referring to FIG. **21B**, an operation of forming an uneven structure on a semiconductor structure **120** may be performed. Specifically, the uneven structure may be formed on the first conductivity-type semiconductor layer **121**. Light extraction efficiency of the semiconductor device package can be improved due to the uneven structure. On the other hand, an uneven structure of a passivation layer **163** may be formed after both the intermediate layer **164** and the passivation layer **163** are disposed, but the present invention is not limited thereto.

(262) Referring to FIG. **21C**, an operation of arranging the passivation layer **163** on the semiconductor structure **120** and an exposed channel layer **130** and forming holes H2-1 and H2-2 such that end portions **151c** and **152c** of interconnection lines **151** and **152** are partially exposed may be performed. In this case, the holes H2-1 and H2-2 may be formed through etching from an etched region S.

(263) That is, the semiconductor structure **120** may be insulated and protected by the passivation layer **163**. In this case, the passivation layer **163** may also include the uneven structure due to the uneven structure of the semiconductor structure **120**.

(264) In addition, a second-first hole H2-1 may be formed such that a first end portion **151c** is exposed, and a second-second hole H2-2 may be formed such that a second end portion **152c** is exposed. That is, the second-first hole H2-1 may be formed by etching the channel layer **130** and a first insulating layer **161** from the passivation layer **163**. The second-second hole H2-2 may be formed by etching the channel layer **130** from the passivation layer **163**.

(265) Referring to FIG. **21D**, an operation of arranging first and second pads **181** and **182** in the etched region of the semiconductor structure **120** may be performed. In this case, the first and second pads **181** and **182** may include first regions **181a** and **182a** and second regions **181b** and **182b**.

(266) Specifically, the first regions **181a** and **182a** may be disposed in the second-first and second-second holes H2-1 and H2-2, respectively. That is, the second regions **181b** and **182b** may be disposed to protrude from the first regions **181a** and **182a** disposed in the second-first and second-second holes H2-1 and H2-2 to the etched region of the semiconductor structure **120**.

(267) The first region **181a** of the first pad **181** may be electrically connected to the first end portion **151c** of the first interconnection line **151**. The first region **181a** may pass through the first insulating layer **161**, the channel layer **130**, and the passivation layer **163**. The second region **181b** of the first pad **181** may protrude outward from the passivation layer **163** and be disposed at a side portion of the semiconductor structure **120**.

(268) The first region **182a** of the second pad **182** may be electrically connected to the second end portion **152c** of the second interconnection line **152**. The first region **182a** may pass through the channel layer **130** and the passivation layer **163**. The second region **182b** of the second pad **182** may protrude outward from the passivation layer **163** and be disposed at the side portion of the semiconductor structure **120**.

(269) Meanwhile, in the drawings, although one first pad **181** and one second pad **182** are disposed, substantially, a plurality of first pads **181** and a plurality of second pads **182** may be present as in the semiconductor structures **120** and the first and second interconnection lines **151** and **152**.

(270) As described above, in the present invention, a semiconductor structure in a large unit may be formed, and the semiconductor structure may be isolated on the substrate **170** to be separated into the semiconductor structures **120** in a chip unit. In addition, peripheral portions of the semiconductor structures corresponding to a peripheral portion of the substrate **170** may be etched together, and the first and second pads **181** and **182** may be disposed in regions in which the semiconductor structure is etched. In this case, the first and second interconnection lines **151** and **152** electrically connected to the semiconductor structure **120** may be disposed to extend to a lower portion of the etched region. Therefore, connections between the first and second pads **181** and **182** and the interconnection lines can be easily performed.

(271) That is, a plurality of semiconductor structures **120** may be disposed on one substrate **170**, and the plurality of first pads **181** and the plurality of second pads **182** may be disposed along the peripheral portion of the substrate **170**. In this case, one first pad **181** and one second pad **182** may be electrically connected to the plurality of semiconductor structures **120**. In addition, the first and second interconnection lines **151** and **152** may be formed between the semiconductor structure **120** and the substrate **170**.

(272) Accordingly, wire bonding for connecting individual chips (semiconductor devices) on a substrate and a package substrate can be omitted to miniaturize a package. In addition, processability can be improved by shortening a process. In addition, a semiconductor region can be further expanded by saving an unnecessary space.

(273) The above-described semiconductor device package is formed as a light-emitting device package and may be used as a light source of a lighting system. For example, the semiconductor device package may be used as a light source of an image display apparatus, a light source of a lighting device, or the like.

(274) The semiconductor device package may be used as an edge-type backlight unit or a direct-type backlight unit when used as a backlight unit of the image display apparatus, and the semiconductor device package may be used in a lighting apparatus or as a bulb-type lighting device when used as the light source of the lighting device. In addition, the semiconductor device package may also be used as a light source of a mobile phone or a headlamp for a vehicle.

(275) While the present invention has been mainly described with reference to the embodiments, it should be understood that the present invention is not limited to the disclosed embodiments and that various modifications and applications may be devised by those skilled in the art without departing from the gist of the present invention. For example, each component specifically shown in the embodiment may be modified and implemented.

(276) Differences related to these modifications and applications should be construed as being within the scope of the present invention defined by the appended claims.

Claims

1. A semiconductor device package comprising: a substrate; a plurality of semiconductor structures disposed to be spaced apart from each other at a central portion of the substrate, wherein the semiconductor structure is disposed on the substrate and comprises a first conductivity-type semiconductor layer, a second conductivity-type semiconductor layer disposed on the first conductivity-type semiconductor layer, and an active layer disposed between the first conductivity-type semiconductor layer and the second conductivity-type semiconductor layer; a first recess formed to pass through the second conductivity-type semiconductor layer, the active layer and extends to a partial region of the first conductivity-type semiconductor layer; a first electrode disposed on the first conductivity-type semiconductor layer and electrically connected to the first

conductivity-type semiconductor layer; a second electrode disposed below the second conductivity-type semiconductor layer and electrically connected to the second conductivity-type semiconductor layer; a plurality of first interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the first conductivity-type semiconductor layer through the first electrode; a plurality of second interconnection lines disposed between the substrate and the plurality of semiconductor structures and electrically connected to the second conductivity-type semiconductor layer through the second electrode; and a reflective layer disposed between the second electrode and the second interconnection line, wherein the first electrode is disposed in the first recess.

2. The semiconductor device package of claim 1, further comprising: a passivation layer disposed on the semiconductor structure and comprising a plurality of layers; and an intermediate layer disposed inside the passivation layer.

3. The semiconductor device package of claim 2, wherein the passivation layer is disposed on an outermost surface of the first conductivity-type semiconductor layer and a portion of an upper surface of the first conductivity-type semiconductor layer.

4. The semiconductor device package of claim 3, wherein the plurality of layers comprise: a first passivation layer disposed to be in contact with the outermost surface and the portion of the upper surface of the first conductivity-type semiconductor layer; a second passivation layer disposed on the first passivation layer, wherein the intermediate layer is disposed between the first passivation layer and the second passivation layer.

5. The semiconductor device package of claim 2, wherein the intermediate layer extends from an outermost surface of the first conductivity-type semiconductor layer to an edge of the substrate.

6. The semiconductor device package of claim 2, wherein the intermediate layer comprises a plurality of layers and is made of any one selected from among metal, ceramic, and semiconductor materials.

7. The semiconductor device package of claim 2, wherein a ratio of a thickness of the intermediate layer to a maximum height of an outermost surface of the first conductivity-type semiconductor layer on a lower surface of the first conductivity-type semiconductor layer is in a range of 1:11.25 to 1:30.

8. The semiconductor device package of claim 2, further comprising: a fluorescent layer disposed on the plurality of semiconductor structures and the passivation layer.

9. The semiconductor device package of claim 8, wherein a ratio of a maximum height of an outermost surface of the first conductivity-type semiconductor layer to a thickness of the fluorescent layer is in a range of 1:1.1 to 1:2.3.

10. The semiconductor device package of claim 1, further comprising: a first insulating layer disposed between the first interconnection line and the second interconnection line; a plurality of first pads electrically connected to the first interconnection lines; and a plurality of second pads electrically connected to the second interconnection lines, wherein the semiconductor structure is disposed between the first pad and the second pad.

11. The semiconductor device package of claim 10, wherein the first interconnection line comprises a first through-portion, which passes through the active layer, the second conductivity-type semiconductor layer and the first insulating layer, and is electrically connected to the first electrode, a first end portion, which extends to an edge of the substrate and is electrically connected to the first pad, and a first connection portion, which is disposed between the first through-portion and the end portion, and the second interconnection line comprises a second end portion that extends to the edge of the substrate and is electrically connected to the second pad.

12. The semiconductor device package of claim 1, wherein an upper surface of the first conductivity-type semiconductor layer comprises a first surface, a second surface disposed below the first surface, and an inclined surface positioned between the first surface and the second surface.

13. The semiconductor device package of claim 12, wherein a ratio of a height from a lower surface of the first conductivity-type semiconductor layer to the second surface to a height from the lower surface exposed by the first recess to the first surface is in a range of 1:1 to 1:10.
 14. The semiconductor device package of claim 12, wherein a length of the second surface in a direction perpendicular to a thickness direction of the semiconductor structure is in a range of 10 μm to 150 μm .
 15. The semiconductor device package of claim 1, wherein a maximum height of an outermost surface of the first conductivity-type semiconductor layer is in a range of 1 μm to 3 μm .
 16. The semiconductor device package of claim 1, wherein a length ratio of a minimum separation distance between adjacent semiconductor structures to a maximum width of the semiconductor structure is in a range of 1:5 to 1:20.
 17. The semiconductor device package of claim 1, wherein an upper surface of the first conductivity-type semiconductor layer is formed with an uneven structure.
-