

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent
Kind Code
Date of Patent
Inventor(s)

12417782
B2
September 16, 2025
Shi; Ning et al.

Multilayer structures for magnetic recording devices to facilitate targeted magnetic switching and low coercivity

Abstract

Aspects of the present disclosure generally relate to magnetic recording heads (such as write heads of data storage devices) that include multilayer structures to facilitate targeted switching and relatively low coercivity. In one or more embodiments, a magnetic recording head includes an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure, a first crystalline layer formed of a first material, and a second crystalline layer between the first crystalline layer and the FeCo layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer. The crystalline structure of the FeCo layer has a texture of <100>.

Inventors: Shi; Ning (San Jose, CA), York; Brian R. (San Jose, CA), Okamura; Susumu (San Jose, CA), Song; Suping (Fremont, CA)

Applicant: Western Digital Technologies, Inc. (San Jose, CA)

Family ID: 1000008820346

Assignee: Western Digital Technologies, Inc. (San Jose, CA)

Appl. No.: 18/637904

Filed: April 17, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240282333 A1	Aug. 22, 2024

Related U.S. Application Data

division parent-doc US 17854617 20220630 US 11990163 child-doc US 18637904

Publication Classification

Int. Cl.: G11B5/39 (20060101)

U.S. Cl.:

CPC G11B5/3929 (20130101); G11B5/3912 (20130101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3794835	12/1973	Hirai	148/DIG.72	H01L 31/109
5948553	12/1998	Kamijo	324/252	H01F 10/3204
7522377	12/2008	Jiang et al.	N/A	N/A
7914916	12/2010	Inturi et al.	N/A	N/A
8329320	12/2011	Zhang et al.	N/A	N/A
9805743	12/2016	Wang et al.	N/A	N/A
11990163	12/2023	Shi	N/A	G11B 5/1278
2001/0055185	12/2000	Ooshima	360/324.11	B82Y 25/00
2004/0125513	12/2003	Tanaka	29/603.18	G11B 5/3906
2005/0069730	12/2004	Doerner	360/135	G11B 5/676
2006/0057430	12/2005	Kuboki	428/836.2	G11B 5/7368
2006/0240289	12/2005	Mizuno	428/815	G11B 5/3929
2008/0112091	12/2007	Shimazawa	N/A	B82Y 10/00
2008/0212239	12/2007	Kawato	N/A	G11B 5/3912
2008/0253024	12/2007	Miyata	360/234.3	G11B 5/3116
2009/0251951	12/2008	Yoshikawa	365/158	G11C 11/1675
2011/0020668	12/2010	Zeltser	428/811.1	B82Y 10/00
2012/0154081	12/2011	Suzuki	427/131	G11B 5/3909
2013/0229728	12/2012	Brinkman	427/535	G11B 5/3116
2021/0390977	12/2020	Freitag	N/A	G11B 5/314
2024/0005951	12/2023	Shi	N/A	G11B 5/3912
2024/0282333	12/2023	Shi	N/A	G11B 5/3929

OTHER PUBLICATIONS

Wang, Xuan et al., "Preparation of soft magnetic FeCo-based films for writers", Journal of Applied Physics, vol. 105, Issue 7, Mar. 2009, <<http://dx.doi.org/10.1063/1.3078008>>. cited by applicant

Gunther, Scheunert et al., "A review of high magnetic moment thin films for microscale and nanotechnology applications", Applied Physics Reviews, Feb. 2016, pp. 1-4, <<https://www.osti.gov/biblio/1338947>>. cited by applicant

Tagawa, Ikuya et al., "High-Performance Write Head Design and Materials", Dec. 2001, pp. 164-173, <<https://www.fujitsu.com/global/documents/about/resources/publications/fstj/archives/vol37-2/paper07.pdf>>. cited by applicant

Sun, N. X. et al., "Stress, microstructure, and magnetic softness of high saturation magnetization

„Bs . . . FeCON films”, American Institute of Physics, Journal of Applied Physics, May 2005, <<https://www.researchgate.net/publication/252592757>>. cited by applicant

Akansel, Serkan et al., “Effect of seed layers on dynamic and static magnetic properties of Fe₆₅Co₃₅ thin films”, Journal of Physics D: Applied Physics, vol. 51, Jul. 2018, <<https://doi.org/10.1088/1361-6463/aaccc0>>. cited by applicant

Katada, H. et al., Soft magnetic properties and microstructure in NiFe/FeCo/NiFe films with large saturation magnetization, IEEE International Magnetism Conference, 2002, <<https://ieeexplore.ieee.org/document/1000670>>. cited by applicant

Herzer, G. “Grain size dependence of coercivity and permeability in nanocrystalline ferromagnets”, IEEE Transactions on Magnetism, vol. 26, No. 5, Sep. 1990, pp. 1397-1402, <<https://sci-hub.se/10.1109/20.104389>>. cited by applicant

Punkkinen, M.P.J. et al., “Surface properties of 3d transition metals”, Philosophical Magazine, vol. 91, No. 27, Sep. 2011, <<https://sci-hub.se/https://doi.org/10.1080/14786435.2011.586953>>. cited by applicant

O’Handley, Robert C., “Modern Magnetic Materials: Principles And Applications”, Nov. 1999, pp. 179-183, <<https://vdoc.pub/documents/modern-magnetic-materials-principles-and-applications-5q71nkp7jtb0>>. cited by applicant

Primary Examiner: Agustin; Peter Vincent

Attorney, Agent or Firm: Patterson + Sheridan, LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a divisional of co-pending U.S. patent application Ser. No. 17/854,617, filed Jun. 30, 2022, which is herein incorporated by reference.

BACKGROUND OF THE DISCLOSURE

Field of the Disclosure

(1) Aspects of the present disclosure generally relate to magnetic recording heads (such as write heads of data storage devices) that include multilayer structures to facilitate targeted switching and relatively low coercivity.

Description of the Related Art

(2) The heart of the functioning and capability of a computer is the storing and writing of data to a data storage device, such as a hard disk drive (HDD). The volume of data processed by a computer is increasing rapidly. There is a need for higher recording density of a magnetic recording medium to increase the function and the capability of a computer.

(3) The volume of data processed by a computer is increasing rapidly. There is a need for higher recording density of a magnetic recording medium (such as recording densities exceeding 2 Tbit/in.² for a magnetic recording medium) to increase the function and the capability of a computer.

(4) To facilitate high recording densities and operational efficiency, multiple aspects may be used. For example, the write and read signals may be pulsed. As another example, ferromagnetic materials with small grains can be used to facilitate softer magnetic responses.

(5) However, challenges can arise. For example, because of the nature of modern magnetic record heads, non-uniform magnetic fields can result in non-uniform switching of grains where the grains are intergranularly exchange coupled. As a result, unintentional switching of neighboring grains can occur. This unintentional parasitic switching of grains can involve large amounts of

unnecessary energy expenditures, hindering the writing process.

(6) Therefore, there is a need for magnetic recording heads that simply and effectively facilitate targeted high density magnetic switching at relatively low coercivities while reducing or eliminating effects on neighboring grains.

SUMMARY OF THE DISCLOSURE

(7) Aspects of the present disclosure generally relate to magnetic recording heads (such as write heads of data storage devices) that include multilayer structures to facilitate targeted switching and relatively low coercivity. In one or more embodiments, a magnetic recording head includes an iron-cobalt (FeCo) layer having a crystalline structure that is body-centered cubic (BCC), a first crystalline layer formed of a first material, and a second crystalline layer between the first crystalline layer and the FeCo layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer. The crystalline structure of the FeCo layer has a texture of $\langle 100 \rangle$.

(8) In one implementation, a magnetic recording head includes an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure, a first crystalline layer formed of a first material; and a second crystalline layer between the first crystalline layer and the FeCo layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer.

(9) In one implementation, a magnetic recording head includes a lower pole, an upper pole, a main pole between the upper pole and the lower pole, and one or more shield structures between the upper pole and the main pole. At least one of the main pole, the lower pole, the upper pole, or the one or more shield structures includes a multilayer structure. The multilayer structures includes an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure.

(10) In one implementation, a magnetic recording head includes a ferromagnetic layer. The magnetic recording head includes a first crystalline layer formed of a first material, and a second crystalline layer between the first crystalline layer and the ferromagnetic layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the ferromagnetic layer and the first crystalline layer.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) So that the manner in which the above recited features of the present disclosure can be understood in detail, a more particular description of the disclosure, briefly summarized above, may be had by reference to embodiments, some of which are illustrated in the appended drawings. It is to be noted, however, that the appended drawings illustrate only typical embodiments of this disclosure and are therefore not to be considered limiting of its scope, for the disclosure may admit to other equally effective embodiments.

(2) FIG. 1 illustrates a schematic view of a disk drive, according to one implementation.

(3) FIG. 2 is a fragmented and schematic cross-sectional side view through a center of a read/write head facing the magnetic media, according to one implementation.

(4) FIG. 3A is a schematic cross-sectional throat view of a magnetic recording head, according to one implementation.

(5) FIG. 3B is a schematic media facing surface cross-sectional view of the magnetic recording head shown in FIG. 3A, according to one implementation.

(6) FIG. 3C is an enlarged view of the schematic media facing surface cross-sectional view of the magnetic recording head shown in FIG. 3B, according to one implementation.

(7) FIG. 4 is a schematic view of a multilayer structure, according to one implementation.

(8) FIG. 5 is a schematic perspective view of a crystal structure of the FeCo layer shown in FIG. 4,

according to one implementation.

(9) FIG. 6 is a schematic plane view of the crystal structure of the FeCo layer shown in FIG. 4 taken along the (100) plane, according to one implementation.

(10) FIG. 7 is a schematic plane view of the crystal structure of the FeCo layer shown in FIG. 4 taken along the (110) plane, according to one implementation.

(11) FIG. 8 is a schematic block diagram view of a method of making the multilayer structure, according to one implementation.

(12) FIG. 9A is a schematic grain view of a plurality of grains of a layer, according to one implementation.

(13) FIG. 9B is a schematic graphical view of a gradient of the localized magnetic field applied in FIG. 9A, according to one implementation.

(14) FIG. 10A is a schematic grain view of a plurality of grains of the FeCo layer shown in FIG. 4, due to exchange coupling, according to one implementation.

(15) FIG. 10B is a schematic graphical view of the same gradient of the localized magnetic field shown in FIG. 9B, according to one implementation.

(16) FIG. 11 is a schematic graphical view of a graph showing energy needed to magnetically switch individual grains of the plurality of grains shown in FIG. 9A under a uniform field, according to one implementation.

(17) FIG. 12 is a schematic graphical view of a graph showing energy needed to magnetically switch individual decoupled grains of the plurality of grains shown in FIG. 10A under a uniform field, according to one implementation.

(18) FIG. 13 is a graphical view of a graph showing magnetocrystalline anisotropy of a BCC crystalline structure, according to one implementation.

(19) FIG. 14 is a schematic graphical view of a graph showing surface energies of various materials, according to one implementation.

(20) FIGS. 15A and 15B are schematic table views of tables showing testing data of FeCo layers for various implementations.

(21) FIG. 16 is a schematic graphical view of a graph showing X-Ray Powder Diffraction (XRD) testing results.

(22) FIG. 17 is a Finite Element Modeling result of an actual write head as presented in a graph 1700 showing effective write field (H_{eff}) at different Hot Seed permeabilities (200, 400, 600), according to one implementation.

(23) FIG. 18 is a Finite Element Modeling result of an actual write head as presented in a graph 1800, according to one implementation.

(24) To facilitate understanding, identical reference numerals have been used, where possible, to designate identical elements that are common to the figures. It is contemplated that elements disclosed in one embodiment may be beneficially utilized on other embodiments without specific recitation.

DETAILED DESCRIPTION

(25) In the following, reference is made to embodiments of the disclosure. However, it should be understood that the disclosure is not limited to specific described embodiments. Instead, any combination of the following features and elements, whether related to different embodiments or not, is contemplated to implement and practice the disclosure. Furthermore, although embodiments of the disclosure may achieve advantages over other possible solutions and/or over the prior art, whether or not a particular advantage is achieved by a given embodiment is not limiting of the disclosure. Thus, the following aspects, features, embodiments and advantages are merely illustrative and are not considered elements or limitations of the appended claims except where explicitly recited in a claim(s). Likewise, reference to “the disclosure” shall not be construed as a generalization of any inventive subject matter disclosed herein and shall not be considered to be an element or limitation of the appended claims except where explicitly recited in a claim(s).

(26) Aspects of the present disclosure generally relate to magnetic recording heads (such as write heads of data storage devices) that include multilayer structures to facilitate targeted high areal density switching and relatively low coercivity. In one or more embodiments, a magnetic recording head includes an iron-cobalt (FeCo) layer having a crystalline structure that is body-centered cubic (BCC), a first crystalline layer formed of a first material, and a second crystalline layer between the first crystalline layer and the FeCo layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer. The crystalline structure of the FeCo layer has a BCC orientation texture of $\langle 100 \rangle$. The first crystalline layer is formed of an alloy, and the second crystalline layer is formed of chromium (Cr). The second crystalline layer has a crystalline structure that is body-centered cubic (BCC) and has a texture of $\langle 100 \rangle$. The first crystalline layer has a crystalline structure that is ordered BCC (such as B2) and has a texture of $\langle 100 \rangle$. The crystalline structure of the first crystalline layer can be any ordered structure, such as B2.

(27) The aspects described herein facilitate targeted magnetic switching at low coercivities in a manner that is simple, reliable, efficient, and cost-effective. The lower coercivities and targeted switching facilitate enhanced writing efficiencies, enhanced overwrite performance, increased linear density and recording density, reduced pole erasure (such as erasure from the main pole), reduced cross track interference (xTI) degradation, and less write field leakage from shield structures (such as from a trailing shield). The lower coercivities also facilitate using soft shield materials for shield structures, which facilitates operational efficiencies.

(28) Aspects of the present disclosure relate to data storage devices using a write head. The write head can be an energy-assisted magnetic recording (EAMR) write head, a microwave-assisted magnetic recording (MAMR) write head, or a heat-assisted magnetic recording (HAMR) write head.

(29) Unless specified otherwise, the chemicals referred to herein can have any number of atoms for the elements included (e.g., stoichiometric or non-stoichiometric).

(30) FIG. 1 illustrates a schematic view of a disk drive **100**, according to one implementation. As shown, at least one rotatable magnetic media **112** is supported on a spindle **114** and rotated by a disk drive motor **118**. The magnetic recording on each disk is in the form of any suitable patterns of data tracks, such as annular patterns of concentric data tracks on the magnetic media **112**.

(31) At least one slider **113** is positioned near the magnetic media **112**, each slider **113** supporting one or more magnetic head assemblies **121**. As the magnetic media rotates, the slider **113** moves radially in and out over the media surface **122** so that the magnetic head assembly **121** may access different tracks of the magnetic media **112** where data are written. Each slider **113** is attached to an actuator arm **119** by way of a suspension **115**. The suspension **115** provides a slight spring force which biases the slider **113** toward the media surface **122**. Each actuator arm **119** is attached to an actuator means **127**. The actuator means **127** as shown in FIG. 1 may be a voice coil motor (VCM). The VCM includes a coil movable within a fixed magnetic field. The direction and speed of the coil movements are controlled by the motor current signals supplied by a control unit **129**.

(32) During operation of the disk drive **100**, the rotation of the magnetic media **112** generates an air bearing between the slider **113** and the media surface **122** which exerts an upward force or lift on the slider **113**. The air bearing thus counter-balances the slight spring force of suspension **115** and supports slider **113** off and slightly above the magnetic media **112** surface by a small, substantially constant spacing during normal operation. The AC magnetic field generated from the magnetic head assembly **121** lowers the coercivity of the high-coercivity media so that the write elements of the magnetic head assemblies **121** may correctly magnetize the data bits in the magnetic media **112**.

(33) The various components of the disk drive **100** are controlled in operation by control signals generated by the control unit **129**, such as access control signals and internal clock signals. The control unit **129** can include logic control circuits, storage means, and a microprocessor. The control unit **129** generates control signals to control various system operations, such as drive motor

control signals on line **123** and head position and seek control signals on line **128**. The control signals on line **128** provide the desired current profiles to optimally move and position slider **113** to the desired data track on the magnetic media **112**. Write and read signals are communicated to and from write and read heads on the magnetic head assembly **121** by way of recording channel **125**. (34) The above description of a typical magnetic disk storage system and the accompanying illustration of FIG. **1** are for representation purposes only. It should be apparent that disk storage systems may contain a large number of disks and actuators, and each actuator may support a number of sliders.

(35) FIG. **2** is a fragmented and schematic cross-sectional side view through a center of a read/write head **200** facing the magnetic media **112**, according to one implementation. The read/write head **200** may correspond to the magnetic head assembly **121** described in FIG. **1**. The read/write head **200** includes a media facing surface (MFS) **212**, such as an air bearing surface (ABS), a magnetic write head **210**, and a magnetic read head **211**, and is mounted such that the MFS **212** is facing the magnetic media **112**. The read/write head **200** may be an energy-assisted magnetic recording (EAMR) head, a microwave-assisted magnetic recording (MAMR) head, or a heat-assisted magnetic recording (HAMR) head. In FIG. **2**, the magnetic media **112** moves past the write head **210** in the direction indicated by the arrow **232** such that the read/write head **200** moves relative to the magnetic media **112** in the direction indicated by the arrow **234**.

(36) In one embodiment, which can be combined with other embodiments, the magnetic read head **211** is a magnetoresistive (MR) read head that includes an MR sensing element **204** located between MR shields S1 and S2. In one embodiment, which can be combined with other embodiments, the magnetic read head **211** is a magnetic tunnel junction (MTJ) read head that includes a MTJ sensing element **204** located between MR shields S1 and S2. The magnetic fields of the adjacent magnetized regions in the magnetic media **112** are detectable by the MR (or MTJ) sensing element **204** as the recorded bits.

(37) The write head **210** includes a return pole **206**, a main pole **220**, a trailing shield **240**, and a coil **218** that excites the main pole **220**. The coil **218** may have a “pancake” structure which winds around a back-contact between the main pole **220** and the return pole **206**, instead of a “helical” structure shown in FIG. **2**. A trailing gap and a leading gap may be in contact with the main pole, and a leading shield may be in contact with the leading gap. A recording magnetic field (e.g., a write field) is generated from the main pole **220** and the trailing shield **240** facilitates making the magnetic field gradient of the main pole **220** steep. The main pole **220** may be a magnetic material such as an FeCo alloy. The main pole **220** may include a trailing surface **222** which may be parallel to a leading surface **236** of the trailing shield **240**. The main pole **220** may be a tapered write pole (TWP) with a trailing edge taper (TET) configuration. In one embodiment, which can be combined with other embodiments, the main pole **220** has a saturated magnetization (M_s) of 2.4 T and a thickness of about 300 nanometers (nm). The trailing shield **240** may be a magnetic material such as NiFe alloy. In one embodiment, which can be combined with other embodiments, the trailing shield **240** has an M_s of about 1.6 T.

(38) FIG. **3A** is a schematic cross-sectional throat view of a magnetic recording head **300**, according to one implementation. The magnetic recording head **300** may be used in a magnetic recording device, such as a hard disk drive (HDD). In one embodiment, which can be combined with other embodiments, the magnetic recording head **300** is used as at least part of the write head **210** shown in FIG. **2**. The present disclosure contemplates that although aspects herein are described in relation to a write head (such as the write head **210**), such aspects can be used in relation to a read head (such as the read head **211**).

(39) It is to be understood that the magnetic recording head discussed herein is applicable to a data storage device such as a hard disk drive (HDD) as well as a tape drive such as a tape embedded drive (TED) or an insertable tape media drive. An example TED is described in co-pending patent application titled “Tape Embedded Drive,” U.S. application Ser. No. 16/365,034, filed Mar. 31,

2019, assigned to the same assignee of this application, which is herein incorporated by reference. As such, any reference in the detailed description to an HDD or tape drive is merely for exemplification purposes and is not intended to limit the disclosure unless explicitly claimed. Furthermore, reference to or claims directed to magnetic recording devices are intended to include both HDD and tape drive unless HDD or tape drive devices are explicitly claimed.

(40) The magnetic recording head **300** includes a lower pole **301**, an upper pole **302**, and a main pole **303** between the upper pole **302** and the lower pole **301**. The magnetic recording head **300** also includes a leading shield **304** on a leading side **305** of the main pole **303**, and a trailing shield **306** on a trailing side **307** of the main pole **303**. The magnetic recording head **300** includes a media facing surface (MFS) **315**, such as an air bearing surface (ABS).

(41) The trailing shield **306** is of a height H1 along the stripe height direction. The height H1 is of 0.5 microns (500 nanometers) or less, such as about 500 nanometers. A trailing side gap **308** is disposed between the main pole **303** and the trailing shield **306**. In one embodiment, which can be combined with other embodiments, the upper pole **302** includes a ledge **313** that protrudes from the upper pole **302** and toward the main pole **303**. The magnetic recording head **300** includes a coil structure **314**. The coil structure **314** can be a “pancake” structure that winds around the trailing side **307** of the main pole **303**, or can be a “helical” structure that winds around the main pole **303**.

(42) FIG. 3B is a schematic media facing surface cross-sectional view of the magnetic recording head **300** shown in FIG. 3A, according to one implementation. Layers **401-404** will be further described in conjunction with FIG. 4, and are shown here to put the layers in context of the overall magnetic head construction. In this example, the layers are shown as a part of the trailing shield **326** but can be implemented in other components of the recording head in various embodiments, as further described below.

(43) FIG. 3C is an enlarged view of the schematic media facing surface cross-sectional view of the magnetic recording head **300** shown in FIG. 3B, according to one implementation.

(44) The magnetic recording head **300** includes a first side gap **320** disposed on a first side **317** of the main pole **303**, and a first side shield **319** disposed on the first side **317** of the main pole **303**. The first side gap **320** is disposed between the main pole **303** and the first side shield **319**. The magnetic recording head **300** includes a second side gap **321** disposed on a second side **318** of the main pole **303**, and a second side shield **322** disposed on the second side **318** of the main pole **303**. The second side gap **321** is disposed between the main pole **303** and the second side shield **322**. The magnetic recording head **300** also includes a leading side gap **323** disposed on the leading side **305** of the main pole **303**. The leading side gap **323** is disposed between the main pole **303** and the leading shield **304**. A hot seed layer **326** is disposed between the main pole **303** and the trailing shield **306**.

(45) The trailing side gap **308** includes a first section **324** between the first side shield **319** and the first side gap **320** (on one side of the first section **324**) and the trailing shield **306** (on another side of the first section **324**). The trailing side gap **308** includes a second section **316** between the main pole **303** and the hot seed layer **326**. The trailing side gap **308** includes a third section **325** between the second side shield **322** and the second side gap **321** (on one side of the third section **325**) and the trailing shield **306** (on another side of the third section **325**). The trailing side gap **308** can extend between the first side shield **319** and the upper pole **302**, and can extend between the second side shield **322** and the upper pole **302**, as is shown in FIG. 3B.

(46) The present disclosure contemplates that one or more of the second section **316**, the first side gap **320**, the second side gap **321**, the leading side gap **323**, the first section **324**, and/or the third section **325** can be a gap.

(47) The present disclosure contemplates that one or more of the second section **316**, the first side gap **320**, the second side gap **321**, the leading side gap **323**, the first section **324**, and/or the third section **325** can be filled with one or more conductive layers that are nonmagnetic. Each of the one or more conductive layers is formed of one or more of ruthenium (Ru), chromium (Cr), tantalum

(Ta), gold (Au), copper (Cu), nickel-chrome (NiCr), nickel-aluminum (NiAl), nickel-tantalum (NiTa), and/or nickel-iron-tantalum (NiFeTa).

(48) The present disclosure contemplates that one or more of the second section **316**, the first side gap **320**, the second side gap **321**, the leading side gap **323**, the first section **324**, and/or the third section **325** can be filled with one or more insulation layers. Each of the one or more insulation layers is formed of one or more of an aluminum oxide (AlO), a silicon nitride (SiN), and/or a tantalum nitride (TaN).

(49) The second section **316** is of a width W1 along a cross-track direction that is about equal to a trailing width TW1 of the main pole **303** along the cross track direction. The width W1 can differ from the trailing width TW1. The width W1 and/or the trailing width TW1 can vary. The trailing side gap **308** is of a thickness T1 along a down-track direction. In one embodiment, which can be combined with other embodiments, the width W1 is within a range of 20 nm to 500 nm. In one embodiment, which can be combined with other embodiments, the thickness T1 is within a range of 10 nm to 100 nm, such as 40 nm. In one embodiment, which can be combined with other embodiments, the width W1 can be up to (such as equal to) a total width TOW1 that includes at least the width W1, a trailing width TW3 of the first side gap **320**, and a trailing width TW4 of the second side gap **321**.

(50) FIG. **4** is a schematic view of a multilayer structure **400**, according to one implementation. The multilayer structure **400** is magnetic. The present disclosure contemplates that the multilayer structure **400** can be conductive or nonconductive.

(51) The multilayer structure **400** includes an amorphous seed layer **401** and an iron-cobalt (FeCo) layer **404** that is ferromagnetic. The FeCo layer **404** includes an Fe atomic percentage within a range of 23% to 100%, and a Co atomic percentage within a range of 0% to 77%. In one or more embodiments, the Co atomic percentage is 75% or less, such as within a range of 65% to 75%. The present disclosure contemplates that the FeCo layer **404** can include one or more impurities (such as nickel (Ni) or nitrogen (N)) having an atomic percentage of 5% or less.

(52) The amorphous seed layer **401** is metallic or ionic. In one embodiment, which can be combined with other embodiments, the amorphous seed layer **401** is formed of a metallic material that includes one or more of nickel (Ni), zirconium (Zr), tantalum (Ta), niobium (Nb), and/or iron (Fe). In one example, which can be combined with other examples, the metallic material includes one or more of nickel-zirconium (NiZr), nickel-tantalum (NiTa), nickel-niobium (NiNb), and/or nickel-tantalum-iron (NiTaFe). Other metallic materials are also contemplated for the amorphous seed layer **401**. In one embodiment, which can be combined with other embodiments, the amorphous seed layer is formed of an ionic material that includes one or more of (Al), oxygen (O), and/or silicon (Si). In one example, which can be combined with other examples, the ionic material includes one or more of aluminum oxide (Al.sub.2O.sub.3) and/or silicon dioxide (SiO.sub.2). Other ionic materials are also contemplated for the amorphous seed layer **401**.

(53) The FeCo layer **404** has a crystalline structure that is body-centered cubic (BCC). The crystalline structure of the FeCo layer **404** has an out-of-plane texture of <100> such that each grain of the FeCo layer **404** is oriented in the <100> out-of-plane axis direction (see FIGS. **5** and **6**). The <100> texture is the crystallographic orientation of each grain within a mosaic spread about the <100> lattice direction. The <100> direction is an out-of-plane direction that extends normal to a film surface of the FeCo layer **404**. The <100> direction of the grains is oriented perpendicularly to, for example, the (010) plane. Other textures, such as <110> and <111>, are contemplated for the FeCo layer **404**. The <100> texture can facilitate targeted or localized magnetic switching while facilitating relatively low coercivity in a spatially pulsed drive field.

(54) The multilayer structure **400** includes a first crystalline layer **402** between the amorphous seed layer **401** and the FeCo layer **404**. The first crystalline layer **402** is formed of a first material. The first crystalline layer **402** is formed of an alloy. The alloy includes one or more ruthenium (Ru), aluminum (Al), chromium (Cr), and/or molybdenum (Mo). Other alloy materials are also

contemplated for the first crystalline layer **402**. In one embodiment, which can be combined with other embodiments, the alloy is a ruthenium aluminide (RuAl) alloy having an Ru atomic percentage within a range of 48% to 58% and an Al atomic percentage within a range of 42% to 52%, such as within a range of 42% to 48%. In one example, which can be combined with other examples, the Al atomic percentage is 45%. In one embodiment, which can be combined with other embodiments, the alloy is a chromium-molybdenum (CrMo) alloy having an Mo atomic percentage within a range of 25% to 60% and a Cr atomic percentage within a range of 40% to 75%. In one or more embodiments, the Mo atomic percentage and the Cr atomic percentage added together equal 100. The first crystalline layer **402** has a crystalline structure that is ordered BCC (B2) and has a texture of $\langle 100 \rangle$.

(55) The multilayer structure **400** includes a second crystalline layer **403** between the first crystalline layer **402** and the FeCo layer **404**. The second crystalline layer **403** is formed of a second material different from the first material. The second crystalline layer **403** interfaces both the FeCo layer **404** and the first crystalline layer **402** such that the second crystalline layer **403** contacts each of the FeCo layer **404** and the first crystalline layer **402**. The second crystalline layer **403** has a crystalline structure that is body-centered cubic (BCC) and has a texture of $\langle 100 \rangle$. Each of the first crystalline layer **402** and the second crystalline layer **403** is non-magnetic. In one or more embodiments, the second crystalline layer **403** is formed of chromium (Cr). In one or more embodiments, the second crystalline layer **403** is formed of an alloy that includes Cr and one or more other materials. In such an embodiment, a Cr atomic percentage is 85% or greater, and/or a total atomic percentage of the one or more other materials is 15% or less.

(56) Other materials are contemplated for the second crystalline layer **403**. In one embodiment, which can be combined with other embodiments, the second crystalline layer **403** includes one or more of chromium (Cr), manganese (Mn), iron (Fe), titanium (Ti), vanadium (V), cobalt (Co), nickel (Ni), copper (Cu), niobium (Nb), molybdenum (Mo), tungsten (W), rhenium (Re), and/or tantalum (Ta). The present disclosure contemplates that one or more other transition metals (such as any of the transition metals) may be used. The second crystalline layer **403** has a surface energy. In one embodiment, which can be combined with other embodiments, the surface energy is 2.25 J/m.² or higher, such as 2.5 J/m.² or higher. In one embodiment, which can be combined with other embodiments, the surface energy is 3.0 J/m.² or higher. The Cr of the second crystalline layer **403** has a relatively high surface energy and beneficial adhesion properties. The relatively high surface energy facilitates lateral grain growth for the FeCo layer **404** over nucleation to reduce (e.g., minimize) surface energy of the FeCo layer **404**. The Cr (compared to other materials) is relatively reactive and relatively easy to adhere (e.g., bond) to other materials (such as the first crystalline layer **402** and the FeCo layer **404**), while having a relatively high surface energy to facilitate large lateral grain growth of the FeCo layer **404**.

(57) Other implementations are contemplated for the first crystalline layer **402**, the second crystalline layer **403**, and the FeCo layer **404**. In one or more implementations, which can be combined with other implementations, each of the first crystalline layer **402**, the second crystalline layer **403**, and the FeCo layer **404** has a crystalline structure that is a cubic lattice structure. In one or more implementations, the crystalline structure is BCC. In one or more implementations, the crystalline structure is ordered BCC (such as B2). In one or more implementations, the crystalline structure is a super lattice cell that can include a plurality of BCC lattice sub-cells or ordered BCC lattice sub-cells (such as a super lattice cell that is DO3, C1B, L12, or CF16). Ordered BCC (B2) can be referred to as CsCl.

(58) Each of the first crystalline layer **402**, the second crystalline layer **403**, and the FeCo layer **404** has a lattice parameter within a range of 2.85 to 3.15. In the implementation shown in FIG. 4, the second crystalline layer **403** is formed of chromium (Cr) and has a surface energy within a range of 3.0 J/m.² to 3.2 J/m.². The Cr of the second crystalline layer **403** facilitates easy and effective functioning and switching of the FeCo layer **404** under a spatially localized pulse field.

Chromium (Cr) can particularly facilitate forming the FeCo layer **404** to facilitate lower coercivities and targeted magnetic switching under a localized drive field. The relatively high surface energy of the second crystalline layer **403** facilitates large grain growth for the FeCo layer **404**.

(59) The first crystalline layer **402** interfaces both the amorphous seed layer **401** and the second crystalline layer **403** such that the first crystalline layer **402** contacts each of the amorphous seed layer **401** and the second crystalline layer **403**.

(60) The amorphous seed layer **401** facilitates reduced interference of other structure underneath the amorphous seed layer **401** (such as structure of the magnetic recording head **300**) with the formation (e.g., epitaxial growth) of the crystalline structures of the first crystalline layer **402**, the second crystalline layer **403**, and the FeCo layer **404**.

(61) The multilayer structure **400** includes an overall thickness OT1 made up of thicknesses T2-T5. The overall thickness OT1 is within a range of 190 Angstroms to 2,300 Angstroms. A first thickness T2 of the amorphous seed layer **401** is within a range of 30 Angstroms to 500 Angstroms. A second thickness T3 of the first crystalline layer **402** is within a range of 30 Angstroms to 100 Angstroms. A third thickness T4 of the second crystalline layer **403** is within a range of 30 Angstroms to 200 Angstroms. A fourth thickness T5 of the FeCo layer **404** is within a range of 100 Angstroms to 1500 Angstroms. The thicknesses OT1, T2, T3, T4, T5 facilitates effective layer functioning (such as the second thickness T3 for functioning of the first crystalline layer **402** and/or the third thickness T4 for functioning of the second crystalline layer **403**). Other values are contemplated for the thicknesses OT1, T2, T3, T4, and/or T5. As an example, the present disclosure contemplates that the overall thickness OT1 can be within a range of 100 Angstroms to 1500 Angstroms.

(62) The multilayer structure **400** can be part of one or more structures of magnetic recording heads, such as the magnetic recording head **300**. In one embodiment, which can be combined with other embodiments, at least one of the main pole **303**, the lower pole **301**, the upper pole **302**, or one or more shield structures (such as the side shield(s) **319**, **322**, the leading shield **304**, and/or the trailing shield **306**) includes the multilayer structure **400**.

(63) In the implementation shown in FIG. 3B, at least the trailing shield **306** includes the multilayer structure **400**. The multilayer structure **400** facilitates targeted (e.g., localized) switching and lower coercivity. The multilayer structure **400** can be particularly beneficial when used as part of the trailing shield **306** because field intensity can be highest across the trailing shield **306** such that the energy needed to switch the field can be highest across the trailing shield **306**.

(64) In another embodiment, the present disclosure additionally contemplates, besides the example of FIG. 3B, that one or more of the amorphous seed layer **401**, the first crystalline layer **402**, and/or the second crystalline layer **403** can be at least part of the gap **316**, and/or the FeCo layer **404** can be at least part of the hot seed layer **326**.

(65) FIG. 5 is a schematic perspective view of a crystal structure **500** of the FeCo layer **404** shown in FIG. 4, according to one implementation. The crystal structure **500** shows the BCC structure of atoms **501** of the FeCo layer **404**. FIG. 5 shows a $\langle 100 \rangle$ direction, a $\langle 110 \rangle$ direction, and a $\langle 111 \rangle$ direction.

(66) FIG. 6 is a schematic plane view of the crystal structure **500** of the FeCo layer **404** shown in FIG. 4 taken along the (100) plane, according to one implementation.

(67) FIG. 7 is a schematic plane view of the crystal structure **500** of the FeCo layer **404** shown in FIG. 4 taken along the (110) plane, according to one implementation.

(68) Magnetic switching along the $\langle 100 \rangle$ direction consumes less energy than magnetic switching along the $\langle 110 \rangle$ direction, and magnetic switching along the $\langle 110 \rangle$ direction consumes less energy than magnetic switching along the $\langle 111 \rangle$ direction.

(69) FIG. 8 is a schematic block diagram view of a method **800** of making the multilayer structure **400**, according to one implementation.

(70) Operation **802** includes forming the amorphous seed layer **401**.

(71) Operation **804** includes forming the first crystalline layer **402** on the amorphous seed layer **401**.

(72) Operation **806** includes forming the second crystalline layer **403** on the first crystalline layer **402**.

(73) Optional operation **808** includes forming a cap layer on the second crystalline layer **403**. In one or more embodiments, the cap layer is formed of ruthenium (Ru). Other materials are contemplated for the cap layer.

(74) Optional operation **810** includes removing the cap layer.

(75) Operation **812** includes forming a third crystalline layer (e.g., the FeCo layer **404**) on the second crystalline layer **403**. In implementations where optional operations **808**, **810** are used, the second crystalline layer **403** is exposed as a result of the removal of the cap layer.

(76) In one or more embodiments, optional operations **808**, **810** are not included in the method **800** if the amorphous seed layer, the first crystalline layer, the second crystalline layer, and the third crystalline layer can be formed in-situ without breaking vacuum in a continuous process. In one or more embodiments, optional operations **808**, **810** are included in the method **800** if one or more layers (such as the third crystalline layer) is formed ex-situ (e.g., breaking vacuum).

(77) The formation of layers of operations **802**, **804**, **806**, and **808** can be conducted in-situ in the same first processing chamber. The removal operation **810** can be conducted in-situ with the formation of operation **812** in the same first processing chamber. The formation of layers of operations **802**, **804**, **806**, and **812** can be conducted in-situ in the same first processing chamber, and optional operations **808**, **810** can be omitted. In one embodiment, which can be combined with other embodiments, the formation of operations **802**, **804**, **806**, **808**, and **812** each includes epitaxially growing the respective layers. Other formation methods are contemplated.

(78) Each operation **802**, **808**, **806**, **808**, and/or **812** can include pre-etching prior to the formation of the respective layer. The pre-etching etches the surface upon which the respective layer is subsequently formed to facilitate adhesion of the respective layer to the etched surface. As an example, an exposed surface of the second crystalline layer is etched prior to the formation of the third crystalline layer in operation **812**.

(79) FIG. **9A** is a schematic grain view of a plurality of grains **901** of a layer, according to one implementation. A localized magnetic field **910** is applied to a first grain **901a** and part of the surrounding grains (such as **901b**, **901c**, etc.).

(80) FIG. **9B** is a schematic graphical view of a gradient **920** of the localized magnetic field **910** applied in FIG. **9A**, according to one implementation. The gradient **920** represents a single pulse of magnetic energy. The gradient **920** shows amplitude of the pulse (vertically) relative to distance (horizontally).

(81) As shown in FIG. **9B**, the gradient **920** is steep to facilitate efficient (e.g., low energy expenditure) and effective magnetic switching. As shown in FIG. **9A**, the localized magnetic field **910** switches not only the magnetization of the first grain **901a** but also the magnetizations of neighboring grains (such as two grains **901b**, **901c**, and the rest of grains shown outside of the spatial pulse **920** in FIG. **9A**). The perturbation outside of the localized pulse is from intergranular ferromagnetic exchange coupling. The unintentional switching of neighboring grains makes it difficult to conduct targeted magnetic switching of single grains.

(82) Each of the grains **901** has a grain size D1. The mean grain size D1 across the plurality of grains **901** is less than the critical exchange couple length, which in one instance is believed to be on the order of 18 nm. The grain size D1 shown refers to the mean side-to-side diameter of the grains **901**.

(83) FIG. **10A** is a schematic grain view of a plurality of grains **1001** of the FeCo layer **404** shown in FIG. **4**, due to exchange coupling, according to one implementation. The same localized magnetic field **910** applied in FIG. **9A** is applied to a single grain **1001a** in FIG. **10A**, and the grain

1001a has a grain size larger than the critical ferromagnetic exchange coupling length, so the single grain **1001a** can switch without perturbing neighboring grains.

(84) FIG. **10B** is a schematic graphical view of the same gradient **920** of the localized magnetic field **910** shown in FIG. **9B**, according to one implementation.

(85) Using the same localized magnetic field **910** having the same gradient **920**, a targeted magnetic switching of the single grain **1001a** is accomplished, as shown in FIG. **10A**. Neighboring grains (such as two grains **1001b**, **1001c**) are not magnetically switched.

(86) Each of the grains **1001** has a grain size **D2**. The mean grain size **D2** across the plurality of grains **901** is 18 nm or higher. In one embodiment, which can be combined with other embodiments, the mean grain size **D2** is 18 nm or higher, such as 20.0 nm or higher. Using the grain size **D2**, grains **1001** are less effected by the magnetizations of neighboring grains compared to the grains **901** shown in FIG. **9A** due to lack of intergranular ferromagnetic exchange coupling.

(87) FIG. **11** is a schematic graphical view of a graph **1100** showing energy needed to magnetically switch individual grains of the plurality of grains **901** shown in FIG. **9A** under a uniform field, according to one implementation. The graph **1100** shows the energy barriers for switching various grains.

(88) An energy barrier profile **1101** of a first grain shows a first energy level **1102** of the first grain. The peak of the profile **1101** represents the energy barrier for switching the first grain. An energy barrier profile **1105** of a second grain shows a second energy level **1104** of the second grain. An energy barrier profile **1107** of an N.sup.th grain shows a third energy level **1106** of the N.sup.th grain.

(89) Due to the relatively small grain size, the ferromagnetic coupling effects among grains are relatively high. When grain size is small and grains are ferromagnetically exchange coupled, aggregates of grains are aligned due to ferromagnetic exchange coupling, and magnetic domain is larger than grain size. As a first energy barrier **1102**, a second energy barrier **1104**, and a third energy barrier **1106** show, the energy states of individual randomly oriented grains may not be the lowest at the bottoms of the energy wells.

(90) FIG. **12** is a schematic graphical view of a graph **1200** showing energy needed to magnetically switch individual decoupled grains of the plurality of grains **1001** shown in FIG. **10A** under a uniform field, according to one implementation. The graph **1200** shows the energy barriers for switching various grains. An energy barrier profile **1201** of a first grain shows a first energy level **1202** of the first grain. The peak of the profile **1201** represents the energy barrier for switching the first grain. An energy barrier profile **1205** of a second grain shows a second energy level **1204** of the second grain. An energy barrier profile **1207** of an N.sup.th grain shows a third energy level **1106** of the N.sup.th grain.

(91) When grain size is large and grains are not ferromagnetically exchange coupled (as shown in FIG. **12**), aggregates of grains are not pre-aligned due to ferromagnetic exchange coupling, and individual grains are sitting in the bottom of respective energy wells as shown in FIG. **12** at the first energy level **1202**, the second energy level **1204**, and the third energy level **1206**.

(92) When a uniform field is applied to switch grains, the sum of total energy spent from the energy levels **1102**, **1104**, **1106** of FIG. **11** will be much less than that from the energy levels **1202**, **1204**, **1206** of FIG. **12**.

(93) This means the coercivity as tested from a film coupon from a tester with uniform field (e.g., a BH Loop and VSM) can provide opposite results compared to results from a magnetic recording head with pulsed field. That is, testing may incorrectly indicate that crystalline with hard intrinsic coercivity may switch more freely than small grain film. Hence, it would be more desirable if FeCo intrinsic magnetization responses can be improved. For example, the functionality of the FeCo layer **404** (shown in FIG. **4**) with large grains (e.g., in FIG. **10A**) may be improved under localized excitation, such as in a recording head.

(94) Because of exchange coupling of grains, the various grains of the plurality of grains **901** tend

to switch in tandem at different applied energies and/or different times. Targeted switching can be difficult because an energy applied to the N.sup.th grain may unintentionally switch the first grain and the second grain, and vice-versa. Hence, targeted magnetic switching of a targeted single grain or a targeted plurality of grains can be difficult to achieve using the grains **901**.

(95) As shown by the energy levels **1202**, **1204**, **1206**, the various grains of the plurality of grains **1001** are decoupled and switch individually at substantially the same applied energy and time. Hence, targeted magnetic switching of a targeted single grain or a targeted plurality of grains can be facilitated using the grains **1001** of the FeCo layer **404** of the multilayer structure **400**. FIG. **13** is a schematic graphical view of a graph **1300** showing magnetocrystalline anisotropy of a BCC crystalline structure, according to one implementation. The vertical axis plots the magnetization moment (in emu/cm.sup.3) of each orientation. The horizontal axis plots applied field. The saturation field correlates to corresponding coercivity (in Oe).

(96) A first profile **1301** shows the magnetic saturation along $\langle 100 \rangle$ orientation.

(97) A second profile **1302** shows the magnetic saturation along $\langle 110 \rangle$ orientation.

(98) A third profile **1303** shows the magnetic saturation along $\langle 111 \rangle$ orientation.

(99) As shown by the first profile **1301**, the $\langle 100 \rangle$ orientation is the easiest magnetization axis. That is, when there is a $\langle 100 \rangle$ texture there are more in-plane easy orientation axes $\langle 100 \rangle$ (in FIG. **6** there are two perpendicular in-plane $\langle 100 \rangle$ axes shown) as opposed to other textures (such as $\langle 110 \rangle$, which is shown in FIG. **7** with one in-plane $\langle 100 \rangle$ axis). The $\langle 100 \rangle$ texture for the FeCo layer **404** facilitates more degrees of freedom to switch during writing operations, and particularly a higher moment at lower coercivities. The more degrees of freedom facilitate a lower electromagnetic energy needed to switch grains, which facilitates more effective magnetic switching, resulting in higher areal density drive capacity with sharper transition and less driving field (see, for example, FIGS. **17** and **18**).

(100) The crystallographic plane with the most in-plane $\langle 100 \rangle$ easy axes is the (100) plane having two orthogonal $\langle 100 \rangle$ easy axes as shown FIG. **6**. That is, a $\langle 100 \rangle$ orientation texture has the most degrees of freedom for magnetizations to facilitate easy switching. Other planes such as (110) have, for example, only one $\langle 100 \rangle$ easy axis is in-plane as shown in FIG. **7**.

(101) The amorphous seed layer **401** facilitates formation of the first crystalline layer **402** and the second crystalline layer **403**. The first crystalline layer **402** facilitates the $\langle 100 \rangle$ texture (having grains in the $\langle 100 \rangle$ direction) for the second crystalline layer **403** and the FeCo layer **404**. The second crystalline layer **403** facilitates lateral grain growth (e.g., relatively large grains) of the FeCo layer **404** to facilitate achieving localized easy switching for the FeCo layer **404**.

(102) The information shown in FIG. **13** can be obtained from Robert C. O'Handley, "Modern Magnetic Materials, Principles and Applications," Pages 179-183.

(103) FIG. **14** is a schematic graphical view of a graph **1400** showing surface energies of various materials, according to one implementation. The vertical axis plots the surface energy.

(104) A first profile **1401** (having solid circles) plots the surface energies of the elements shown in a row **1411** adjacent the bottom horizontal axis.

(105) A second profile **1402** (having hollow triangles) plots the surface energies of the elements shown in a first row **1412** adjacent the top horizontal axis.

(106) A first profile **1403** (having hollow squares) plots the surface energies of the elements shown in a second row **1413** adjacent the top horizontal axis. The second row **1413** of elements is below the first row **1412** of elements.

(107) The surface energy of each element is determined by finding the value that vertically aligns with the element in the graph **1400** along the respective profile **1401**, **1402**, or **1403**.

(108) The information shown in FIG. **14** can be obtained from M. P. J. Punkkinen, et al., "Surface properties of 3d transition metals," 2011, *Philosophical Magazine*, 91:27, Pages 3627-3640.

(109) As discussed above, Cr has a relatively high surface energy (which facilitates large lateral grain growth) and beneficial adhesion and oxidation properties.

(110) FIGS. 15A and 15B are schematic table views of tables showing testing data of FeCo layers for various implementations.

(111) FIG. 15A shows an easy axis coercivity “H_{ce},” an easy axis squareness “S_{qe},” a hard axis coercivity “H_{ch},” and a hard axis squareness “S_{qh},” and a texture for each of five implementations.

(112) FIG. 15B shows a FeCo layer thickness (in Angstroms), a grain size (in Angstroms), and the texture for four of the five implementations.

(113) “Implementation(s) 1-4” involves various implementations of the method 800 shown in FIG. 8.

(114) “Implementation 1” involves the multilayer structure 400 where the removal of a cap layer is ex-situ relative to the formation of the FeCo layer 404, the first crystalline layer 402 is formed of a ruthenium aluminide (RuAl) alloy and has a <100> texture, the second crystalline layer 403 is formed of chromium (Cr) and is oxidized after formation, and the FeCo layer 404 is formed ex-situ.

(115) “Implementation 2” involves the multilayer structure 400 where the removal of a cap layer is in-situ with FeCo layer 404 deposition, the first crystalline layer 402 is formed of a ruthenium aluminide (RuAl) alloy and has a <100> texture, the second crystalline layer 403 is formed of chromium (Cr) and is not oxidized, and the FeCo layer 404 is formed in-situ.

(116) “Implementation 3” involves the multilayer structure 400 where all of the layers 401, 402, and 403 are omitted, and the FeCo layer 404 is formed on an SiO₂ substrate (including thermally oxidized Si).

(117) “Implementation 4” involves the multilayer structure 400 where the second crystalline layer 403 is formed of chromium (Cr) and has a <110> texture, and the FeCo layer 404 is formed in-situ.

(118) “Implementation 5” involves a FeCo layer formed on nickel-chrome (NiCr) where FeCo is detected to have smaller grains 901, as this FeCo layer is additionally formed of nickel-chrome (NiCr) in addition to iron-cobalt (FeCo), and the FeCo layer is formed in-situ.

(119) As can be seen by comparing FIGS. 15A and 15B, implementations such as “Implementation 1” and “Implementation 2” facilitate large grain sizes and <100> textures, and show significant reduction in hard axis coercivity and reduction of hard axis squareness as compare to Implementation 3 and 4. The data in FIGS. 15A and 15B was obtained from BH Loop measurements. The hard axis coercivity of Implementations 1 and 2 is relatively close to that of Implementation 5, which is induced by small grain intergranular ferromagnetic exchange coupling.

(120) FIG. 16 is a schematic graphical view of a graph 1600 showing out-of-Plane X-Ray Powder Diffraction (XRD) testing results. Various implementations are shown in FIG. 16. The vertical axis plots the square root of the intensity (in counts) of the number of grains having the texture of the respective profile. The horizontal axis plots double the angle of diffraction (in degrees). Each of the profiles shown in the graph 1600 is shown in a logarithmic scale.

(121) A first profile 1601 has a first section 1601a that corresponds to iron-cobalt (FeCo) having greatly reduced <110> diffraction intensity facilitated by the <100> texture, a second section 1601b that corresponds to the ruthenium aluminide (RuAl) alloy having a texture of <200> (shown by measured diffraction), and a third section 1601c that corresponds to the FeCo material having a texture of <200>. All three sections 1601a, 1601b, 1601c indicate the <100> texture.

(122) A second profile 1602, a third profile 1603, and a fourth profile 1604 each corresponds to iron-cobalt (CoFe) having no marginally detectable <200> diffraction and an increasing <110> intensity, consistent with a texture of <110>.

(123) The first profile 1601 corresponds to the multilayer structure 400.

(124) The second profile 1602 corresponds to “Implementation 4” shown in FIGS. 15A and 15B.

(125) The third profile 1603 corresponds to “Implementation 3” shown in FIGS. 15A and 15B.

(126) The fourth profile 1604 corresponds to “Implementation 5” shown in FIGS. 15A and 15B.

(127) FIG. 17 is a Finite Element Modeling result of an actual write head as presented in a graph

1700 showing effective write field (Heff) at different Hot Seed permeabilities (200, 400, 600), according to one implementation. The horizontal axis of the graph **1700** is the bump position (in nm). The higher the permeability, the softer the FeCo film, and the lower the Hch. Profiles **1701** **1702**, **1703** show FeCo film with permeabilities of 200, 400, 600 respectively. By using the multilayer structure **400**, the permeability of the trailing shield **306** and/or the hot seed layer **326** would increase, and the Heff would increase.

(128) The increase of permeability from 200 to 400 raises the profile from **1701** to **1702**, facilitating a gain G1 in overwrite performance. The gain G1 is 0.15 dB or higher.

(129) FIG. **18** is a Finite Element Modeling result of an actual write head as presented in a graph **1800**, according to one implementation. The graph **1800** shows an effective write field gradient (Hgrad) at different Hot Seed permeabilities (200, 400, 600, respectively). The higher the permeability, the softer the FeCo film, and the lower the Hch. Profiles **1801** **1802**, **1803** are FeCo film with permeabilities of 200, 400, 600 respectively. As the permeability of the trailing shield **306** and/or the hot seed layer **326** increases, the Hgrad increases.

(130) The increase of permeability from 200 to 400 raises the profile from **1801** to **1802**, facilitating a gain G2 in linear density of 0.5% or higher (e.g., in bits per inch).

(131) Using the multilayer structure **400**, the permeability of the trailing shield **306** and/or the hot seed layer **326** would increase compared to other operations. Additionally, using the multilayer structure **400**, increased hot seed permeability reduces magnetic leakage to the side shields **319** and **322** that can cause cross track interference and performance degradation. The multilayer structure **400** facilitates reduced performance degradation (such as degradation of the trailing shield **306** and/or the hot seed layer **326**). The degradation is reduced compared leakage that can cause magnetic migration toward the side shields **319**, **322**, which can cause magnetic saturation at edges **381**, **382** (shown in FIG. 3B) of the side shields **319**, **322**. The otherwise degraded performance of the trailing shield **306** and/or the hot seed layer **326** could cause an increase in unshielded magnetic field in the area corresponding to the trailing shield **306** and/or the hot seed layer **326**, which would hinder writing operations.

(132) Additionally, magnetic leakage can cause more magnetic field to be shielded in areas where the magnetic field is less strong (such as in areas corresponding to the side shields **319**, **322**), which can hinder writing operations.

(133) The present disclosure utilizes localized magnetic switching with reduced individual grain coercivities under high magnetic field gradients. Benefits include enhanced writing efficiencies; simplicity; reliability; enhanced overwrite performance; increased linear density and recording density; enhanced reliability by potentially reducing pole erasure from high remanence fields; reduced cross track interference from stray field due to un-saturated and/or under-saturated shield; reduced shield performance degradation; less shield field leakage from shield structures (such as for a trailing shield); using soft shield materials for shield structures; and operational efficiencies. Moreover, certain thin film tests with uniform applied magnetic fields are incapable of resolving the differences between the structures disclosed herein and certain other microstructures such as small grains with “softer magnetic properties,” because both have small coercivity and are magnetically anisotropic. It is under a spatially pulsed magnetic field at the device level during writing operations where the small grain structures with intergranular coupling magnetically drag neighboring and otherwise undisturbed grains along, making switching sluggish and less responsive. Additionally, such an effect from ferromagnetic exchange coupling is undiscoverable during film development and during selection from tests that use uniform fields. A drive test may be used but can be expensive, impractical, and/or time-consuming (such as by taking six months or longer for development cycle times). By mitigating such effects, the present disclosure saves development costs and development cycle times, and facilitates cost effectiveness.

(134) As an example, reduced coercivity in a trailing shield and/or hot seed facilitates increased permeability and reduced or eliminated magnetic leakage that can degrade shield performance. As

another example, reduced coercivity facilitates increased areal density capability (ADC). As another example, reduced coercivity facilitates using recording media (e.g., disks) that have lower coercivities, which facilitates lower write signals and reduced power inputs for writing to facilitate enhanced thermal reliability of magnetic recording devices. The aspects described herein can facilitate the benefits described by, for example, reducing shield leakage to enhance shield performance.

(135) The facilitated large grain sizes with reduced coercivities increases the modularity of certain components (such as the trailing shield **306** and material(s) used) for use with modern HDD's that facilitate high recording density and use of pulsed writing signals.

(136) It is contemplated that one or more aspects disclosed herein may be combined. Moreover, it is contemplated that one or more aspects disclosed herein may include some or all of the aforementioned benefits. As an example, one or more of the aspects, components, features, operations, and/or properties of the magnetic recording head **300**, the multilayer structure **400**, the crystal structure **500**, the method **800**, the grains **1001**, the graph **1200**, the graph **1300**, the graph **1400**, the tables of FIGS. **15A** and **15B**, the graph **1600**, the graph **1700**, and/or the graph **1800** may be combined for a magnetic recording head (such as a write head of an HDD).

(137) In one implementation, a magnetic recording head includes an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure, a first crystalline layer formed of a first material; and a second crystalline layer between the first crystalline layer and the FeCo layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer. The crystalline structure of the FeCo layer is body-centered cubic and has a texture of $\langle 100 \rangle$. The FeCo layer includes a plurality of grains having a mean grain size of 18 nm or higher. The second crystalline layer has a surface energy that is 2.25 J/m² or higher. The second crystalline layer includes chromium (Cr) at a Cr atomic percentage of 85% or greater. The second crystalline layer has a crystalline structure that is body-centered cubic (BCC) and has a texture of $\langle 100 \rangle$. The first crystalline layer is formed of an alloy including one or more ruthenium (Ru), aluminum (Al), chromium (Cr), or molybdenum (Mo). In one or more embodiments, the alloy is a ruthenium aluminide (RuAl) alloy having an Ru atomic percentage within a range of 48% to 58% and an Al atomic percentage within a range of 42% to 48%. In one or more embodiments, the alloy is a chromium-molybdenum (CrMo) alloy having an Mo atomic percentage within a range of 25% to 60% and a Cr atomic percentage within a range of 40% to 75%. The first crystalline layer has a crystalline structure that is ordered BCC (B2) and has a texture of $\langle 100 \rangle$. The magnetic recording head includes an amorphous seed layer. The first crystalline layer is between the amorphous seed layer and the FeCo layer. The amorphous seed layer is metallic or ionic. In one or more embodiments, the amorphous seed layer is formed of a metallic material that includes one or more of nickel (Ni), zirconium (Zr), tantalum (Ta), niobium (Nb), or iron (Fe). In one or more embodiments, the amorphous seed layer is formed of an ionic material that includes one or more of (Al), oxygen (O), or silicon (Si). A magnetic recording device having the magnetic recording head is also disclosed.

(138) In one implementation, a magnetic recording head includes a lower pole, an upper pole, a main pole between the upper pole and the lower pole, and one or more shield structures between the upper pole and the main pole. At least one of the main pole, the lower pole, the upper pole, or the one or more shield structures includes a multilayer structure. The multilayer structure includes an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure. In one or more embodiments, the one or more shield structures include a trailing shield, and the trailing shield includes the multilayer structure. The multilayer structure also includes an amorphous seed layer and a first crystalline layer between the amorphous seed layer and the FeCo layer. The first crystalline layer is formed of a first material. The multilayer structure also includes a second crystalline layer between the first crystalline layer and the FeCo layer. The second crystalline layer

is formed of a second material different from the first material, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer. The crystalline structure of the FeCo layer is body-centered cubic (BCC) and has a texture of <100>, the first crystalline layer is formed of an alloy, and the second crystalline layer includes chromium (Cr) at a Cr atomic percentage of 85% or greater.

(139) In one implementation, a magnetic recording head includes a ferromagnetic layer. The magnetic recording head includes a first crystalline layer formed of a first material, and a second crystalline layer between the first crystalline layer and the ferromagnetic layer. The second crystalline layer is formed of a second material different from the first material, and the second crystalline layer interfaces both the ferromagnetic layer and the first crystalline layer.

(140) While the foregoing is directed to embodiments of the present disclosure, other and further embodiments of the disclosure may be devised without departing from the basic scope thereof, and the scope thereof is determined by the claims that follow.

Claims

1. A magnetic recording head, comprising: a lower pole; an upper pole; a main pole between the upper pole and the lower pole; and one or more shield structures between the upper pole and the main pole; wherein at least one of the main pole, the lower pole, the upper pole, or the one or more shield structures includes a multilayer structure comprising: an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure; a first crystalline layer formed of a first material; and a second crystalline layer formed of a second material different from the first material.
2. The magnetic recording head of claim 1, wherein the one or more shield structures include a trailing shield, and the trailing shield includes the multilayer structure.
3. The magnetic recording head of claim 1, wherein the multilayer structure further comprises: an amorphous seed layer, wherein: the first crystalline layer is disposed between the amorphous seed layer and the FeCo layer, the second crystalline layer is disposed between the first crystalline layer and the FeCo layer, and the second crystalline layer interfaces both the FeCo layer and the first crystalline layer.
4. The magnetic recording head of claim 3, wherein the crystalline structure of the FeCo layer is body-centered cubic (BCC) and has a texture of <100>, and wherein the first crystalline layer is formed of an alloy.
5. The magnetic recording head of claim 4, wherein the second crystalline layer includes chromium (Cr) at a Cr atomic percentage that is 85% or greater.
6. The magnetic recording head of claim 1, wherein the FeCo layer comprises an Fe atomic percentage of about 23% to about 100% and a Co atomic percentage between about 65% to about 75%.
7. The magnetic recording head of claim 1, wherein the FeCo layer comprises a plurality of grains having a mean grain size of 18 nm or higher.
8. A magnetic recording device comprising the magnetic recording head of claim 1.
9. A magnetic recording head, comprising: a ferromagnetic layer; a first crystalline layer formed of a first material; a second crystalline layer between the first crystalline layer and the ferromagnetic layer, the second crystalline layer formed of a second material different from the first material, and the second crystalline layer interfacing both the ferromagnetic layer and the first crystalline layer; and a hot seed layer, the hot seed layer comprising the ferromagnetic layer.
10. The magnetic recording head of claim 9, wherein the ferromagnetic layer comprises iron-cobalt (FeCo).
11. The magnetic recording head of claim 10, further comprising a main pole, wherein: one of more of the first crystalline layer and the second crystalline layer is in a gap between the hot seed layer

and the main pole.

12. The magnetic recording head of claim 10, further comprising a main pole and one or more shields for the main pole, wherein at least one of the one or more shields comprises the ferromagnetic layer.

13. The magnetic recording head of claim 12, wherein the at least one of one or more shields is a trailing shield that comprises the ferromagnetic layer.

14. A magnetic recording device comprising the magnetic recording head of claim 9.

15. A magnetic recording head, comprising: a lower pole; an upper pole; a main pole between the upper pole and the lower pole; and a trailing shield disposed between the main pole and the upper pole, the trailing shield comprising a multilayer structure, wherein the multilayer structure comprises: an amorphous seed layer; an iron-cobalt (FeCo) layer having a crystalline structure that is a cubic lattice structure; a first crystalline layer formed of a first material; and a second crystalline layer between the first crystalline layer and the FeCo layer, the second crystalline layer formed of a second material different from the first material, and the second crystalline layer interfacing both the FeCo layer and the first crystalline layer.

16. The magnetic recording head of claim 15, wherein the crystalline structure of the FeCo layer is body-centered cubic (BCC) and has a texture of $\langle 100 \rangle$.

17. The magnetic recording head of claim 15, wherein the second crystalline layer includes chromium (Cr) at a Cr atomic percentage that is 85% or greater and a surface energy that is 2.25 J/m² or higher.

18. The magnetic recording head of claim 15, wherein the FeCo layer comprises an Fe atomic percentage of about 23% to about 100% and a Co atomic percentage between about 65% to about 75%.

19. The magnetic recording head of claim 15, wherein one of more of the first crystalline layer and the second crystalline layer is in a gap between the FeCo layer and the main pole.

20. A magnetic recording device comprising the magnetic recording head of claim 15.
