

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12418049
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Narita; Kazuhei et al.

Power storage device, method for manufacturing power storage device, and electronic device

Abstract

To provide a power storage device whose charge and discharge characteristics are unlikely to be degraded by heat treatment. To provide a power storage device that is highly safe against heat treatment. The power storage device includes a positive electrode, a negative electrode, a separator, an electrolytic solution, and an exterior body. The separator is located between the positive electrode and the negative electrode. The separator contains polyphenylene sulfide or solvent-spun regenerated cellulosic fiber. The electrolytic solution contains a solute and two or more kinds of solvents. The solute contains LiBETA. One of the solvents is propylene carbonate.

Inventors: Narita; Kazuhei (Kanagawa, JP), Tajima; Ryota (Kanagawa, JP), Oguni; Teppei (Kanagawa, JP)

Applicant: SEMICONDUCTOR ENERGY LABORATORY CO., LTD. (Atsugi, JP)

Family ID: 1000008820331

Assignee: Semiconductor Energy Laboratory Co., Ltd. (Kanagawa-ken, JP)

Appl. No.: 18/613703

Filed: March 22, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240258575 A1	Aug. 01, 2024

Foreign Application Priority Data

JP	2015-240755	Dec. 10, 2015
----	-------------	---------------

Related U.S. Application Data

Publication Classification

Int. Cl.: H01M10/0569 (20100101); G04G19/00 (20060101); H01G11/28 (20130101);
H01G11/32 (20130101); H01G11/52 (20130101); H01G11/60 (20130101); H01G11/62
(20130101); H01G11/84 (20130101); H01G11/86 (20130101); H01M4/36 (20060101);
H01M4/525 (20100101); H01M4/587 (20100101); H01M4/66 (20060101);
H01M10/0525 (20100101); H01M10/0568 (20100101); H01M50/414 (20210101);
H01M50/429 (20210101); H01M50/44 (20210101)

U.S. Cl.:

CPC H01M10/0569 (20130101); G04G19/00 (20130101); H01G11/28 (20130101);
H01G11/32 (20130101); H01G11/52 (20130101); H01G11/60 (20130101); H01G11/62
(20130101); H01G11/84 (20130101); H01G11/86 (20130101); H01M4/366 (20130101);
H01M4/525 (20130101); H01M4/587 (20130101); H01M4/661 (20130101);
H01M4/669 (20130101); H01M10/0525 (20130101); H01M10/0568 (20130101);
H01M50/414 (20210101); H01M50/429 (20210101); H01M50/4295 (20210101);
H01M50/44 (20210101); H01M2300/0037 (20130101); Y02E60/13 (20130101);
Y02T10/70 (20130101)

Field of Classification Search

CPC: H01M (10/0569); H01M (10/0568); H01M (50/4295); H01M (50/414); H01M (50/44);
H01M (50/429); H01M (4/366); H01M (4/525); H01M (4/587); H01M (4/661); H01M
(4/669)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5135694	12/1991	Akahane	264/273	B29C 45/14311
5889737	12/1998	Alameh	368/204	G04G 17/083
6040092	12/1999	Yamada et al.	N/A	N/A
7261972	12/2006	Inada et al.	N/A	N/A
7419747	12/2007	Utsugi et al.	N/A	N/A
7642015	12/2009	Inada et al.	N/A	N/A
8597830	12/2012	Kawakami et al.	N/A	N/A
8663841	12/2013	Tajima et al.	N/A	N/A
8785030	12/2013	Ueda	N/A	N/A
8822088	12/2013	Tajima et al.	N/A	N/A
9070950	12/2014	Kuriki et al.	N/A	N/A
9183995	12/2014	Inoue et al.	N/A	N/A
9368792	12/2015	Lee et al.	N/A	N/A

9401247	12/2015	Tajima et al.	N/A	N/A
9461300	12/2015	Osada et al.	N/A	N/A
9580322	12/2016	Lee et al.	N/A	N/A
9735430	12/2016	Kimura et al.	N/A	N/A
9806305	12/2016	Suzuki et al.	N/A	N/A
10256442	12/2018	Suzuki et al.	N/A	N/A
10320025	12/2018	Hiroki et al.	N/A	N/A
10529990	12/2019	Kimura et al.	N/A	N/A
11316189	12/2021	Hiroki et al.	N/A	N/A
2003/0152839	12/2002	Kawai et al.	N/A	N/A
2004/0224230	12/2003	Yanagida et al.	N/A	N/A
2007/0224516	12/2006	Deguchi et al.	N/A	N/A
2009/0186270	12/2008	Harada et al.	N/A	N/A
2013/0084495	12/2012	Tajima et al.	N/A	N/A
2013/0101884	12/2012	Ueda	429/127	H01M 10/0583
2013/0149605	12/2012	Kakehata et al.	N/A	N/A
2013/0164611	12/2012	Nanba et al.	N/A	N/A
2013/0236781	12/2012	Oguni et al.	N/A	N/A
2013/0249054	12/2012	Kuriki et al.	N/A	N/A
2013/0273405	12/2012	Takahashi et al.	N/A	N/A
2013/0273406	12/2012	Ihara	429/188	H01M 10/0569
2013/0330610	12/2012	Shigematsu et al.	N/A	N/A
2014/0004412	12/2013	Ogino	N/A	N/A
2014/0023920	12/2013	Yamazaki et al.	N/A	N/A
2014/0087251	12/2013	Takahashi et al.	N/A	N/A
2014/0099539	12/2013	Yamazaki et al.	N/A	N/A
2014/0099554	12/2013	Inoue et al.	N/A	N/A
2014/0127566	12/2013	Kuriki et al.	N/A	N/A
2014/0127567	12/2013	Kuriki et al.	N/A	N/A
2014/0356707	12/2013	Kwon et al.	N/A	N/A
2014/0370379	12/2013	Inoue et al.	N/A	N/A
2015/0086868	12/2014	Inoue et al.	N/A	N/A
2015/0132648	12/2014	Inoue et al.	N/A	N/A
2015/0140397	12/2014	Tajima et al.	N/A	N/A
2015/0140400	12/2014	Yamazaki et al.	N/A	N/A
2015/0147626	12/2014	Tajima et al.	N/A	N/A
2015/0155528	12/2014	Takahashi et al.	N/A	N/A
2015/0155530	12/2014	Takahashi et al.	N/A	N/A
2015/0162590	12/2014	Takahashi et al.	N/A	N/A
2015/0194668	12/2014	Ueda	252/182.1	H01M 4/625
2015/0207148	12/2014	Kimura et al.	N/A	N/A
2015/0243962	12/2014	Hiroki et al.	N/A	N/A
2015/0333359	12/2014	Takahashi et al.	N/A	N/A
2015/0333360	12/2014	Tajima et al.	N/A	N/A
2015/0340664	12/2014	Takahashi et al.	N/A	N/A
2015/0349375	12/2014	Takahashi et al.	N/A	N/A
2016/0013469	12/2015	Tajima et al.	N/A	N/A

2016/0020035	12/2015	Inoue et al.	N/A	N/A
2016/0043363	12/2015	Tajima et al.	N/A	N/A
2016/0087305	12/2015	Yoneda et al.	N/A	N/A
2016/0118689	12/2015	Oguni et al.	N/A	N/A
2016/0156012	12/2015	Takahashi et al.	N/A	N/A
2016/0156071	12/2015	Yamakaji et al.	N/A	N/A
2016/0190545	12/2015	Momo et al.	N/A	N/A
2016/0204437	12/2015	Tajima et al.	N/A	N/A
2016/0218387	12/2015	Tajima	N/A	N/A
2016/0240325	12/2015	Tajima et al.	N/A	N/A
2016/0268064	12/2015	Ishikawa et al.	N/A	N/A
2017/0045378	12/2016	Fukuda et al.	N/A	N/A
2017/0117589	12/2016	Tajima et al.	N/A	N/A
2020/0144621	12/2019	Kimura et al.	N/A	N/A
2022/0109178	12/2021	Hiroki et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
001675783	12/2004	CN	N/A
103682258	12/2013	CN	N/A
60-053084	12/1984	JP	N/A
09-274901	12/1996	JP	N/A
2000-173559	12/1999	JP	N/A
2004-014459	12/2003	JP	N/A
2004-087229	12/2003	JP	N/A
2004-127556	12/2003	JP	N/A
2004-319210	12/2003	JP	N/A
2005-228730	12/2004	JP	N/A
3771319	12/2005	JP	N/A
2012-009418	12/2011	JP	N/A
2012-204155	12/2011	JP	N/A
2013-187138	12/2012	JP	N/A
2013-219015	12/2012	JP	N/A
2014-044950	12/2013	JP	N/A
2015-159107	12/2014	JP	N/A
2015-187967	12/2014	JP	N/A
5826419	12/2014	JP	N/A
1999-0028636	12/1998	KR	N/A
2014-0140323	12/2013	KR	N/A
WO-1997/002513	12/1996	WO	N/A
WO-2012/140709	12/2011	WO	N/A

OTHER PUBLICATIONS

Ota.H et al., “Characterization of Lithium Electrode in Lithium Imides/Ethylene Carbonate, and Cyclic Ether Electrolytes”, J. Electrochem. Soc. (Journal of the Electrochemical Society), Feb. 9, 2004, vol. 151, No. 3, pp. 427-436. cited by applicant

Chinese Office Action (Application No. 201611127609.0) dated Oct. 28, 2020. cited by applicant

Campion.C et al., “Thermal Decomposition of LiPF₆-Based Electrolytes for Lithium-Ion

Primary Examiner: Vo; Jimmy

Attorney, Agent or Firm: NIXON PEABODY LLP

Background/Summary

BACKGROUND OF THE INVENTION

1. Field of the Invention

(1) Embodiments of the present invention relate to a power storage device and an electronic device.

(2) Note that one embodiment of the present invention is not limited to the above technical field.

One embodiment of the invention disclosed in this specification and the like relates to an object, a method, or a manufacturing method. One embodiment of the present invention relates to a process, a machine, manufacture, or a composition of matter. Specifically, examples of the technical field of one embodiment of the invention disclosed in this specification include a semiconductor device, a display device, a light-emitting device, a power storage device, a memory device, an imaging device, a driving method thereof, and a manufacturing method thereof.

(3) In this specification, the power storage device is a collective term describing elements and devices that have a power storage function. For example, a power storage device (also referred to as a secondary battery) such as a lithium-ion secondary battery, a lithium-ion capacitor, and an electric double layer capacitor are included in the category of the power storage device.

2. Description of the Related Art

(4) In recent years, a variety of power storage devices, for example, lithium-ion secondary batteries, lithium-ion capacitors, and air cells have been actively developed. In particular, demand for lithium-ion secondary batteries with high output and high energy density has rapidly grown with the development of the semiconductor industry, for portable information terminals such as mobile phones, smartphones, and laptop computers, portable music players, and digital cameras; medical equipment; next-generation clean energy vehicles such as hybrid electric vehicles (HEV), electric vehicles (EV), and plug-in hybrid electric vehicles (PHEV); and the like. The lithium-ion secondary batteries are essential as rechargeable energy supply sources for today's information society.

(5) As described above, lithium-ion secondary batteries have been used for a variety of purposes in various fields. Properties necessary for such lithium-ion secondary batteries are high energy density, excellent cycle performance, safety in a variety of operation environments, and the like.

(6) A lithium-ion secondary battery includes at least a positive electrode, a negative electrode, and an electrolytic solution (Patent Document 1).

REFERENCE

Patent Document

(7) [Patent Document 1] Japanese Published Patent Application No. 2012-009418

SUMMARY OF THE INVENTION

(8) Lithium-ion secondary batteries that are to be mounted in electronic devices such as a wearable device and a portable information terminal need to resist heat treatment performed when the electronic devices are processed. Particularly in the case where a housing of the electronic device and a lithium-ion secondary battery are integrally formed, the lithium-ion secondary battery needs to have heat resistance to a temperature higher than or equal to the manufacturing temperature of the housing.

- (9) An object of one embodiment of the present invention is to provide a power storage device whose charging and discharging characteristics are unlikely to be degraded by heat treatment.
- (10) Another object of one embodiment of the present invention is to provide a power storage device that is highly safe against heat treatment.
- (11) Another object of one embodiment of the present invention is to provide a power storage device having high flexibility. Another object of one embodiment of the present invention is to provide a novel power storage device, a novel electronic device, or the like.
- (12) Note that the description of these objects does not disturb the existence of other objects. In one embodiment of the present invention, there is no need to achieve all the objects. Other objects will be apparent from and can be derived from the description of the specification, the drawings, the claims, and the like.
- (13) One embodiment of the present invention is a power storage device including a positive electrode, a negative electrode, a separator, an electrolytic solution, and an exterior body. The positive electrode includes a positive electrode active material layer and a positive electrode current collector. The negative electrode includes a negative electrode active material layer and a negative electrode current collector. The separator is located between the positive electrode and the negative electrode. The separator contains polyphenylene sulfide or solvent-spun regenerated cellulosic fiber. The electrolytic solution contains a solute and two or more kinds of solvents. The solute contains lithium bis(pentafluoroethanesulfonyl)amide (LiBETA). One of the solvents is propylene carbonate.
- (14) Another embodiment of the present invention is the power storage device in which the solvents include propylene carbonate and ethylene carbonate.
- (15) Another embodiment of the present invention is the power storage device in which the negative electrode active material layer contains graphite.
- (16) Another embodiment of the present invention is the power storage device in which the negative electrode active material layer includes spherical natural graphite. The spherical natural graphite includes a first region and a second region. The first region covers the second region. The first region has lower crystallinity than the second region.
- (17) Another embodiment of the present invention is the power storage device in which the positive electrode active material layer contains LiCoO_2 .
- (18) Another embodiment of the present invention is the power storage device in which the positive electrode current collector contains aluminum or stainless steel.
- (19) Another embodiment of the present invention is a method for manufacturing the power storage device. In the method, a heating step is performed at a first temperature for 10 minutes before energization of the power storage device. The first temperature is higher than or equal to 110°C . and lower than or equal to 190°C .
- (20) Another embodiment of the present invention is an electronic device including the power storage device, a band, a display panel, and a housing. The power storage device includes a positive electrode lead and a negative electrode lead. The positive electrode lead is electrically connected to the positive electrode. The negative electrode lead is electrically connected to the negative electrode. The power storage device is buried in the band. Part of the positive electrode lead and part of the negative electrode lead protrude from the band. The power storage device has flexibility. The power storage device is electrically connected to the display panel. The display panel is included in the housing. The band is connected to the housing. The band includes a rubber material.
- (21) Another embodiment of the present invention is the electronic device in which the rubber material is fluorine rubber or silicone rubber.
- (22) One embodiment of the present invention can provide a power storage device whose charging and discharging characteristics are unlikely to be degraded by heat treatment.
- (23) One embodiment of the present invention can provide a power storage device that is highly safe against heat treatment.

(24) One embodiment of the present invention can provide a power storage device having high flexibility. One embodiment of the present invention can provide a novel power storage device, a novel electronic device, or the like.

(25) Note that the description of these effects does not disturb the existence of other effects. One embodiment of the present invention does not necessarily have all the effects listed above. Other effects will be apparent from and can be derived from the description of the specification, the drawings, the claims, and the like.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIGS. 1A to 1C illustrate an example of a power storage device and examples of electrodes.
- (2) FIGS. 2A and 2B each illustrate an example of a power storage device.
- (3) FIGS. 3A and 3B each illustrate an example of a power storage device.
- (4) FIGS. 4A and 4B each illustrate an example of a power storage device.
- (5) FIGS. 5A to 5F illustrate examples of embossing.
- (6) FIGS. 6A and 6B illustrate an example of a power storage device.
- (7) FIG. 7 illustrates an example of a power storage device.
- (8) FIG. 8 illustrates an example of a power storage device.
- (9) FIGS. 9A to 9C illustrate an example of a method for manufacturing a power storage device.
- (10) FIGS. 10A to 10C illustrate an example of a method for manufacturing a power storage device.
- (11) FIG. 11 illustrates an example of a method for manufacturing a power storage device.
- (12) FIGS. 12A to 12C illustrate examples of an electronic device, a band, and a power storage device.
- (13) FIGS. 13A to 13C illustrate examples of a band and power storage devices.
- (14) FIGS. 14A and 14B illustrate an example of a power storage device.
- (15) FIG. 15A to 15C illustrate an example of a method for detecting leakage.
- (16) FIGS. 16A and 16B illustrate an example of a power storage device.
- (17) FIGS. 17A and 17B illustrate an example of a power storage device.
- (18) FIG. 18 illustrates an example of a power storage device.
- (19) FIGS. 19A to 19D illustrate an example of a method for fabricating a power storage device.
- (20) FIGS. 20A, 20B, 20C1, and 20C2 illustrate an example of a power storage device.
- (21) FIG. 21 illustrates an example of a power storage device.
- (22) FIGS. 22A to 22D illustrate an example of a method for fabricating a power storage device.
- (23) FIG. 23 illustrates an example of a power storage device.
- (24) FIGS. 24A to 24F illustrate examples of electronic devices.
- (25) FIGS. 25A to 25D illustrate examples of electronic devices.
- (26) FIGS. 26A to 26C illustrate an example of an electronic device.
- (27) FIG. 27 illustrates examples of electronic devices.
- (28) FIGS. 28A and 28B illustrate examples of electronic devices.
- (29) FIGS. 29A to 29D each show charge and discharge curves in Example 1.
- (30) FIGS. 30A to 30D each show charge and discharge curves in Example 1.
- (31) FIGS. 31A to 31C are cross-sectional TEM images in Example 2.
- (32) FIG. 32 shows analysis results of Raman spectra in Example 2.
- (33) FIGS. 33A and 33B each show charge and discharge curves in Example 3.

DETAILED DESCRIPTION OF THE INVENTION

(34) Embodiments and an example will be described in detail with reference to drawings. Note that the present invention is not limited to the description below, and it is easily understood by those

skilled in the art that various changes and modifications can be made without departing from the spirit and scope of the present invention. Accordingly, the present invention should not be interpreted as being limited to the content of the embodiments and example below.

(35) Note that in the structures of the invention described below, the same portions or portions having similar functions are denoted by the same reference numerals in different drawings, and the descriptions of such portions are not repeated. Furthermore, the same hatching pattern is applied to portions having similar functions, and the portions are not specially denoted by reference numerals in some cases.

(36) In addition, the position, size, range, or the like of each structure illustrated in drawings and the like is not accurately represented in some cases for easy understanding. Therefore, the disclosed invention is not necessarily limited to the position, size, range, or the like disclosed in the drawings and the like.

(37) Note that the terms “film” and “layer” can be interchanged with each other depending on the case or circumstances. For example, the term “conductive layer” can be changed into the term “conductive film” in some cases. Also, the term “insulating film” can be changed into the term “insulating layer” in some cases.

Embodiment 1

(38) In this embodiment, power storage devices of embodiments of the present invention will be described with reference to FIGS. 1A to 1C to FIG. 11.

(39) The power storage device of one embodiment of the present invention includes a positive electrode, a negative electrode, a separator, an electrolytic solution, and an exterior body. Note that in this specification and the like, the electrolytic solution is not limited to a liquid one and may be a gelled or solid one.

(40) For high heat resistance of the power storage device, first, a solute contained in the electrolytic solution needs to have high stability at high temperature. For example, lithium hexafluorophosphate (LiPF₆), which is widely used as a lithium salt serving as a solute, is decomposed into LiF and PF₅ at high temperature. It is said that PF₅ causes the decomposition of a solvent; thus, LiPF₆ seems to have low stability at high temperature for a solute.

(41) In view of the above, as a solute in the electrolytic solution in the power storage device of one embodiment of the present invention, lithium bis(pentafluoroethanesulfonyl)amide (Li(C₂F₅SO₂)₂N, abbreviation: LiBETA) is preferably used. LiBETA has a decomposition temperature of 350° C., and has high heat resistance. Furthermore, in the case where, for example, aluminum is used for a positive electrode current collector, the use of LiBETA can inhibit aluminum dissolution from the positive electrode current collector because a passivating film is easily formed on a surface of the positive electrode current collector when the power storage device is charged and discharged.

(42) Moreover, to increase the heat resistance of the power storage device, a solvent contained in the electrolytic solution preferably has a high boiling point and low vapor pressure. An example of a nonaqueous solvent having a boiling point of 242° C. is propylene carbonate (PC).

(43) However, in the case where graphite is used as a negative electrode active material, PC does not form a passivating film on a surface of graphite but is intercalated between graphite layers together with lithium ions, separating part of the graphite layers from a graphite particle in some cases.

(44) Thus, the electrolytic solution in the power storage device of one embodiment of the present invention contains two or more kinds of solvents, including at least PC. The solvent in the electrolytic solution other than PC preferably has a function of forming a passivating film on a surface of the negative electrode. Examples of the solvent contained in the electrolytic solution other than PC include ethylene carbonate (EC) and vinylene carbonate (VC).

(45) The boiling point of EC is 248° C., and EC has high heat resistance and low vapor pressure. Depending on a selected graphite material, a mixed solvent of PC and EC can inhibit separation of

a graphite layer. For example, a 1:1 (volume ratio) mixture of PC and EC can be used as the solvent. In the case where graphite is used for the negative electrode, a graphite material in which PC is unlikely to be intercalated between layers is preferably selected. In the power storage device of one embodiment of the present invention, spherical natural graphite is used for the negative electrode active material. The spherical natural graphite includes a region having low crystallinity on the surface side, whereby PC intercalation between layers of the spherical natural graphite may be reduced.

(46) It is confirmed that the following aluminum laminated cell does not expand due to heat treatment performed at 170° C. for 15 minutes. In the aluminum laminated cell, encapsulated is an electrolytic solution in which 1 mol/l of LiBETA is dissolved and PC and EC are mixed at a volume ratio of 1:1. Thus, the solvent in which PC and EC are mixed at a volume ratio of 1:1 has high stability and low vapor pressure at high temperature.

(47) Polyethylene, polypropylene, and the like, which are generally used as a separator, are sensitive to heat. Minute pores of a separator might be blocked at high temperature, resulting in malfunction of the power storage device.

(48) In view of the above, in the power storage device of one embodiment of the present invention, a separator containing polyphenylene sulfide or a separator containing solvent-spun regenerated cellulosic fiber is used.

(49) The separator containing polyphenylene sulfide and the separator containing solvent-spun regenerated cellulosic fiber have high heat resistance and high chemical resistance.

(50) Moreover, the separator containing polyphenylene sulfide and the separator containing solvent-spun regenerated cellulosic fiber have low reactivity to the electrolytic solution at high temperature. Thus, degradation of the output characteristics and the charge and discharge cycle performance can be inhibited.

(51) <Structural Example of Power Storage Device>

(52) Next, a specific structure of the power storage device of one embodiment of the present invention will be described below.

(53) FIG. 1A illustrates a power storage device **500**, which is a power storage device of one embodiment of the present invention. Although FIG. 1A illustrates a mode of a thin power storage device as an example of the power storage device **500**, one embodiment of the present invention is not limited to this example.

(54) As illustrated in FIG. 1A, the power storage device **500** includes a positive electrode **503**, a negative electrode **506**, a separator **507**, and an exterior body **509**. The power storage device **500** may include a positive electrode lead **510** and a negative electrode lead **511**. A bonding portion **518** corresponds to a thermocompression bonding portion in the outer region of the exterior body **509**.

(55) FIGS. 2A and 2B each illustrate an example of a cross-sectional view along dashed-dotted line A1-A2 in FIG. 1A. FIGS. 2A and 2B each illustrate a cross-sectional structure of the power storage device **500** that is formed using a pair of the positive electrode **503** and the negative electrode **506**.

(56) As illustrated in FIGS. 2A and 2B, the power storage device **500** includes the positive electrode **503**, the negative electrode **506**, the separator **507**, an electrolytic solution **508**, and the exterior bodies **509**. The separator **507** is located between the positive electrode **503** and the negative electrode **506**. A space surrounded by the exterior bodies **509** is filled with the electrolytic solution **508**.

(57) The positive electrode **503** includes a positive electrode active material layer **502** and a positive electrode current collector **501**. The negative electrode **506** includes a negative electrode active material layer **505** and a negative electrode current collector **504**. The active material layer is formed on one surface or opposite surfaces of the current collector. The separator **507** is positioned between the positive electrode current collector **501** and the negative electrode current collector **504**.

(58) The power storage device includes one or more positive electrodes and one or more negative

electrodes. For example, the power storage device can have a layered structure including a plurality of positive electrodes and a plurality of negative electrodes.

(59) FIG. 3A illustrates another example of a cross-sectional view along dashed-dotted line A1-A2 in FIG. 1A. FIG. 3B is a cross-sectional view along dashed-dotted line B1-B2 in FIG. 1A.

(60) FIGS. 3A and 3B each illustrate a cross-sectional structure of the power storage device 500 that is formed using a plurality of pairs of the positive and negative electrodes 503 and 506. There is no limitation on the number of electrode layers of the power storage device 500. In the case of using a large number of electrode layers, the power storage device can have high capacity. In contrast, in the case of using a small number of electrode layers, the power storage device can have a small thickness and high flexibility.

(61) The examples in FIGS. 3A and 3B each include two positive electrodes 503 in each of which the positive electrode active material layer 502 is provided on one surface of the positive electrode current collector 501; two positive electrodes 503 in each of which the positive electrode active material layers 502 are provided on opposite surfaces of the positive electrode current collector 501; and three negative electrodes 506 in each of which the negative electrode active material layers 505 are provided on opposite surfaces of the negative electrode current collector 504. In other words, the power storage device 500 includes six positive electrode active material layers 502 and six negative electrode active material layers 505. Note that although the separator 507 has a bag-like shape in the examples illustrated in FIGS. 3A and 3B, the present invention is not limited to this example and the separator 507 may have a strip shape or a bellows shape.

(62) Alternatively, one positive electrode in which both surfaces of the positive electrode current collector 501 are provided with the positive electrode active material layers 502 in FIGS. 3A and 3B is preferably replaced with two positive electrodes in each of which one surface of the positive electrode current collector 501 is provided with the positive electrode active material layer 502. Similarly, one negative electrode in which both surfaces of the negative electrode current collector 504 are provided with the negative electrode active material layers 505 is preferably replaced with two negative electrodes in each of which one surface of the negative electrode current collector 504 is provided with the negative electrode active material layer 505. In the power storage device 500 in FIGS. 4A and 4B, surfaces of the positive electrode current collectors 501 on the side not provided with the positive electrode active material layer 502 face and are in contact with each other, and surfaces of the negative electrode current collectors 504 on the side not provided with the negative electrode active material layer 505 face and are in contact with each other. Such a structure allows the interface between the two positive electrode current collectors 501 and the two negative electrode current collectors 504 to serve as sliding planes when the power storage device 500 is curved, relieving stress caused in the power storage device 500.

(63) FIG. 1B illustrates the appearance of the positive electrode 503. The positive electrode 503 includes the positive electrode current collector 501 and the positive electrode active material layer 502.

(64) FIG. 1C illustrates the appearance of the negative electrode 506. The negative electrode 506 includes the negative electrode current collector 504 and the negative electrode active material layer 505.

(65) The positive electrode 503 and the negative electrode 506 preferably include tab regions so that a plurality of stacked positive electrodes can be electrically connected to each other and a plurality of stacked negative electrodes can be electrically connected to each other. Furthermore, a lead is preferably electrically connected to the tab region.

(66) As illustrated in FIG. 1B, the positive electrode 503 preferably includes the tab region 281. The positive electrode lead 510 is preferably welded to part of the tab region 281. The tab region 281 preferably includes a region where the positive electrode current collector 501 is exposed. When the positive electrode lead 510 is welded to the region where the positive electrode current collector 501 is exposed, contact resistance can be further reduced. Although FIG. 1B illustrates the

example where the positive electrode current collector **501** is exposed in the entire tab region **281**, the tab region **281** may partly include the positive electrode active material layer **502**.

(67) As illustrated in FIG. **1C**, the negative electrode **506** preferably includes the tab region **282**. The negative electrode lead **511** is preferably welded to part of the tab region **282**. The tab region **282** preferably includes a region where the negative electrode current collector **504** is exposed. When the negative electrode lead **511** is welded to the region where the negative electrode current collector **504** is exposed, contact resistance can be further reduced. Although FIG. **1C** illustrates the example where the negative electrode current collector **504** is exposed in the entire tab region **282**, the tab region **282** may partly include the negative electrode active material layer **505**.

(68) Although FIG. **1A** illustrates the example where the ends of the positive electrode **503** and the negative electrode **506** are substantially aligned with each other, part of the positive electrode **503** may extend beyond the end of the negative electrode **506**.

(69) In the power storage device **500**, the area of a region where the negative electrode **506** does not overlap with the positive electrode **503** is preferably as small as possible.

(70) In the example illustrated in FIG. **2A**, the end of the negative electrode **506** is located inward from the end of the positive electrode **503**. With this structure, the entire negative electrode **506** can overlap with the positive electrode **503** or the area of the region where the negative electrode **506** does not overlap with the positive electrode **503** can be small.

(71) The areas of the positive electrode **503** and the negative electrode **506** in the power storage device **500** are preferably substantially equal. For example, the areas of the positive electrode **503** and the negative electrode **506** that face each other with the separator **507** therebetween are preferably substantially equal. For example, the areas of the positive electrode active material layer **502** and the negative electrode active material layer **505** that face each other with the separator **507** therebetween are preferably substantially equal.

(72) For example, as illustrated in FIGS. **3A** and **3B**, the area of the positive electrode **503** on the separator **507** side is preferably substantially equal to the area of the negative electrode **506** on the separator **507** side. When the area of a surface of the positive electrode **503** on the negative electrode **506** side is substantially equal to the area of a surface of the negative electrode **506** on the positive electrode **503** side, the region where the negative electrode **506** does not overlap with the positive electrode **503** can be small (does not exist, ideally), whereby the power storage device **500** can have reduced irreversible capacity. Alternatively, as illustrated in FIGS. **3A** and **3B**, the area of the surface of the positive electrode active material layer **502** on the separator **507** side is preferably substantially equal to the area of the surface of the negative electrode active material layer **505** on the separator **507** side.

(73) As illustrated in FIGS. **3A** and **3B**, the end of the positive electrode **503** and the end of the negative electrode **506** are preferably substantially aligned with each other. Ends of the positive electrode active material layer **502** and the negative electrode active material layer **505** are preferably substantially aligned with each other.

(74) In the example illustrated in FIG. **2B**, the end of the positive electrode **503** is located inward from the end of the negative electrode **506**. With this structure, the entire positive electrode **503** can overlap with the negative electrode **506** or the area of the region where the positive electrode **503** does not overlap with the negative electrode **506** can be small. In the case where the end of the negative electrode **506** is located inward from the end of the positive electrode **503**, a current sometimes concentrates at the end portion of the negative electrode **506**. For example, concentration of a current in part of the negative electrode **506** results in deposition of lithium on the negative electrode **506** in some cases. By reducing the area of the region where the positive electrode **503** does not overlap with the negative electrode **506**, concentration of a current in part of the negative electrode **506** can be inhibited. As a result, for example, deposition of lithium on the negative electrode **506** can be inhibited, which is preferable.

(75) As illustrated in FIG. **1A**, the positive electrode lead **510** is preferably electrically connected to

the positive electrode **503**. Similarly, the negative electrode lead **511** is preferably electrically connected to the negative electrode **506**. The positive electrode lead **510** and the negative electrode lead **511** are exposed to the outside of the exterior body **509** so as to serve as terminals for electrical contact with an external portion.

(76) The positive electrode current collector **501** and the negative electrode current collector **504** can double as terminals for electrical contact with an external portion. In that case, the positive electrode current collector **501** and the negative electrode current collector **504** may be arranged such that part of the positive electrode current collector **501** and part of the negative electrode current collector **504** are exposed to the outside of the exterior body **509** without using leads.

(77) Note that part of a surface of the exterior body **509** preferably has projections and depressions. This can relieve stress applied to the exterior body **509** when the power storage device **500** is curved. Thus, the power storage device **500** can have high flexibility. Such projections and depressions can be formed by embossing the exterior body **509** before the power storage device **500** is assembled.

(78) Here, embossing, which is a kind of pressing, will be described.

(79) FIGS. **5A** to **5F** are cross-sectional views illustrating examples of embossing. Note that embossing refers to processing for forming unevenness on a film by bringing an embossing roll whose surface has unevenness into contact with the film with pressure. Note that the embossing roll is a roll whose surface is patterned.

(80) FIG. **5A** illustrates an example where one surface of a film **50** used for the exterior body **509** is embossed.

(81) FIG. **5A** illustrates the state where a film **50** is sandwiched between an embossing roll **53** in contact with the one surface of the film and a roll **54** in contact with the other surface and the film **50** is transferred in a direction **60**. The surface of the film is patterned by pressure or heat.

(82) Processing illustrated in FIG. **5A** is called one-side embossing, which can be performed by a combination of the embossing roll **53** and the roll **54** (a metal roll or an elastic roll such as a rubber roll).

(83) FIG. **5B** illustrates the state where a film **51** whose one surface is embossed is sandwiched between the embossing roll **53** and the roll **54** and is transferred in the direction **60**. The embossing roll **53** rolls along a non-embossed surface of the film **51**; thus, both surfaces of the film **51** are embossed. As described here, one film can be embossed more than once.

(84) FIG. **5C** is an enlarged view of a cross section of a film **52** whose both surfaces are embossed. Note that H.sub.1 represents the thickness of the film in depressions or projections, and H.sub.2 represents the thickness of the film at a boundary portion between a depression and its adjacent projection or the thickness of the film at a boundary portion between a projection and its adjacent depression. The thickness of the film is not uniform, and H.sub.2 is smaller than H.sub.1.

(85) FIG. **5D** illustrates another example where both surfaces of a film are embossed.

(86) FIG. **5D** illustrates the state where the film **50** is sandwiched between the embossing roll **53** in contact with one surface of the film and an embossing roll **55** in contact with the other surface and the film **50** is being transferred in the direction **60**.

(87) FIG. **5D** illustrates a combination of the embossing roll **53** and the embossing roll **55**, which are a couple of embossing rolls. The surface of the film **50** is patterned by alternately provided projections and depressions for embossing and debossing part of the surface of the film **50**.

(88) FIG. **5E** illustrates the case of using the embossing roll **53** and an embossing roll **56** whose protrusions have a pitch different from that of protrusions of the embossing roll **55** in FIG. **5D**. Note that a protrusion pitch or an embossing pitch is the distance between the tops of adjacent protrusions. For example, a distance **P** in FIG. **5E** is a protrusion pitch or an embossing pitch. FIG. **5E** illustrates the state where the film **50** is sandwiched between the embossing roll **53** and the embossing roll **56** and is transferred in the direction **60**. The film processed using the embossing rolls with different protrusion pitches can have surfaces with different embossing pitches.

(89) FIG. 5F illustrates the state where the film 50 is sandwiched between an embossing roll 57 in contact with one surface of the film and an embossing roll 58 in contact with the other surface and the film 50 is transferred in the direction 60.

(90) Processing illustrated in FIG. 5F is called tip-to-tip both-side embossing performed by a combination of the embossing roll 57 and the embossing roll 58 that has the same pattern as the embossing roll 57. The phases of the projections and depressions of the two embossing rolls are coordinate, so that substantially the same pattern can be formed on both surfaces of the film 50. Unlike in the case of FIG. 5E, embossing may be performed without coordinating the phases of the projections and depressions of the same embossing rolls.

(91) An embossing plate can be used instead of the embossing roll. Furthermore, embossing is not necessarily employed, and any method that allows formation of a relief on part of the film can be employed.

(92) FIG. 6A illustrates an example of the power storage device 500 using an exterior body 529 having projections and depressions formed by the embossing described above. FIG. 6B is a cross-sectional view taken along the dashed-dotted line H1-H2 in FIG. 6A. The structure of FIG. 6B without the exterior body 529 is similar to the structure of FIG. 3B.

(93) The projections and depressions of the exterior body 529 are formed so as to include a region overlapping with the positive electrode 503 and the negative electrode 506. In FIG. 6A, the bonding portion 518 does not have projections and depressions, but may have projections and depressions.

(94) Furthermore, the projections and depressions of the exterior body 529 are formed at regular intervals in the long axis direction of the power storage device 500 (the Y direction in FIG. 6A). In other words, one depression and one projection are formed so as to extend in the short axis direction of the power storage device 500 (the X direction in FIG. 6A). Such projections and depressions can relieve stress applied when the power storage device 500 is curved in the long axis direction.

(95) Note that the projections and depressions of the exterior body 529 may be formed so as to have a geometric pattern in which diagonal lines in two directions cross each other (see FIG. 7). Such projections and depressions can relieve stresses caused by curving the power storage device 500 in at least two directions.

(96) Although the positive electrode lead 510 and the negative electrode lead 511 are provided on the same side of the power storage device 500 in FIG. 1A, the positive electrode lead 510 and the negative electrode lead 511 may be provided on different sides of the power storage device 500 as illustrated in FIG. 8. The leads of the power storage device of one embodiment of the present invention can be freely positioned as described above; therefore, the degree of freedom in design is high. Accordingly, a product including the power storage device of one embodiment of the present invention can have a high degree of freedom in design. Furthermore, a yield of products each including the power storage device of one embodiment of the present invention can be increased.

(97) <Example of Manufacturing Method for Power Storage Device>

(98) Next, an example of a manufacturing method for the power storage device 500, which is a power storage device of one embodiment of the present invention, will be described with reference to FIGS. 9A and 9B to FIG. 11.

(99) First, the positive electrode 503, the negative electrode 506, and the separator 507 are stacked. Specifically, the separator 507 is positioned over the positive electrode 503. Then, the negative electrode 506 is positioned over the separator 507. In the case of using two or more positive electrode-negative electrode pairs, another separator 507 is positioned over the negative electrode 506, and then, the positive electrode 503 is positioned. In this manner, the positive electrodes 503 and the negative electrodes 506 are alternately stacked and separated by the separator 507.

(100) Alternatively, the separator 507 may have a bag-like shape. The electrode is preferably surrounded by the separator 507, in which case the electrode is less likely to be damaged during a

fabricating process.

(101) First, the positive electrode **503** is positioned over the separator **507**. Then, the separator **507** is folded along a broken line in FIG. **9A** so that the positive electrode **503** is sandwiched by the separator **507**. Although the example where the positive electrode **503** is sandwiched by the separator **507** is described here, the negative electrode **506** may be sandwiched by the separator **507**.

(102) Here, the outer edges of the separator **507** outside the positive electrode **503** are bonded so that the separator **507** has a bag-like shape (or an envelope-like shape). The bonding of the outer edges of the separator **507** can be performed with the use of an adhesive or the like, by ultrasonic welding, or by thermal fusion bonding.

(103) Next, the outer edges of the separator **507** are bonded by heating. Bonding portions **514** are illustrated in FIG. **9A**. In such a manner, the positive electrode **503** can be covered with the separator **507**.

(104) Note that in the case where a material such as cellulose or paper is used as the separator **507**, the outer edges of the separator **507** are bonded using an adhesive or the like. The amount of the adhesive is preferably small. The outer edges of the separator **507** are bonded such that an electrode (the positive electrode **503** in FIG. **9A**) sandwiched between facing portions of the separator **507** does not protrude from the separator **507**; thus, for example, when the bonding portions **514** are formed as illustrated in FIG. **9B**, the amount of the adhesive can be reduced. In FIG. **9B**, the bonding portions **514** are formed at the following portions of the outer edges of the separator **507**: portions of two sides intersecting with a side where a fold is formed that are close to the fold; and a portion of a side opposite to the side where the fold is formed.

(105) Then, the positive electrodes **503** each covered with the separator **507** and the negative electrodes **506** are alternately stacked as illustrated in FIG. **9C**. Furthermore, the positive electrode lead **510** and the negative electrode lead **511** each having a sealing layer **115** are prepared.

(106) After that, the positive electrode lead **510** having the sealing layer **115** is connected to the tab region **281** of the positive electrode **503** as illustrated in FIG. **10A**. FIG. **10B** is an enlarged view of a connection portion. The tab region **281** of the positive electrode **503** and the positive electrode lead **510** are electrically connected to each other by irradiating the bonding portion **512** with ultrasonic waves while applying pressure thereto (ultrasonic welding). In that case, a curved portion **513** is preferably provided in the tab region **281**.

(107) This curved portion **513** can relieve stress due to external force applied after fabrication of the power storage device **500**. Thus, the power storage device **500** can have high reliability.

(108) The negative electrode lead **511** can be electrically connected to the tab region **282** of the negative electrode **506** by a similar method.

(109) Subsequently, the positive electrode **503**, the negative electrode **506**, and the separator **507** are positioned over an exterior body **509**.

(110) Then, the exterior body **509** is folded along a portion shown by a dotted line in the vicinity of a center portion of the exterior body **509** in FIG. **10C**.

(111) In FIG. **11**, the thermocompression bonding portion in the outer edges of the exterior body **509** is illustrated as a bonding portion **118**. The outer edges of the exterior body **509** except an inlet **119** for introducing the electrolytic solution **508** are bonded by thermocompression bonding. In thermocompression bonding, sealing layers provided over the leads are also melted, thereby fixing the leads and the exterior body **509** to each other. Moreover, adhesion between the exterior body **509** and the leads can be increased.

(112) After that, in a reduced-pressure atmosphere or an inert gas atmosphere, a desired amount of electrolytic solution **508** is introduced to the inside of the exterior body **509** from the inlet **119**.

Lastly, the inlet **119** is sealed by thermocompression bonding. Through the above steps, the power storage device **500**, which is a thin power storage device, can be fabricated.

(113) Aging may be performed after fabrication of the power storage device **500**. The aging can be

performed under the following conditions, for example. Charging is performed at a rate of 0.001 C or more and 0.2 C or less at temperatures higher than or equal to room temperature and lower than or equal to 50° C. In the case where an electrolytic solution is decomposed and a gas is generated and accumulates between the electrodes, the electrolytic solution cannot be in contact with a surface of the electrode in some regions. That is to say, an effectual reaction area of the electrode is reduced and effectual resistance is increased.

(114) When the resistance is extremely increased, the negative electrode potential is decreased. Consequently, lithium is intercalated into graphite and lithium is deposited on the surface of graphite. The lithium deposition might reduce capacity. For example, if a coating film or the like is grown on the surface after lithium deposition, lithium deposited on the surface cannot be dissolved again. This lithium cannot contribute to capacity. In addition, when deposited lithium is physically collapsed and conduction with the electrode is lost, the lithium also cannot contribute to capacity. Therefore, the gas is preferably released to prevent the potential of the negative electrode from reaching the potential of lithium because of an increase in a charging voltage.

(115) In the case of performing degasification, for example, part of the exterior body of the thin power storage device is cut to open the power storage device. When the exterior body is expanded because of a gas, the form of the exterior body is preferably adjusted. Furthermore, the electrolytic solution may be added as needed before resealing. In the case where degasification cannot be performed, a space for releasing a gas may be provided in the cell so that a gas that accumulates between the electrodes can be released from between the electrodes. Alternatively, a space formed by the use of the embossed laminate exterior body described above can be utilized as a space for releasing a gas.

(116) After the release of the gas, the charging state may be maintained at temperatures higher than room temperature, preferably higher than or equal to 30° C. and lower than or equal to 60° C., more preferably higher than or equal to 35° C. and lower than or equal to 50° C. for, for example, 1 hour or more and 100 hours or less. In the initial charging, an electrolytic solution decomposed on the surface forms a coating film. The formed coating film may thus be densified when the charging state is held at temperatures higher than room temperature after the release of the gas, for example.

(117) <Components of Power Storage Device>

(118) Components of the power storage device of one embodiment of the present invention will be described in detail below. When a flexible material is selected from materials of the members described in this embodiment and used, a flexible power storage device can be fabricated.

(119) <<Separator>>

(120) In the power storage device of one embodiment of the present invention, a separator containing polyphenylene sulfide or solvent-spun regenerated cellulosic fiber is used. The separator can have either a single-layer structure or a layered structure, and may have a layered structure of a separator containing solvent-spun regenerated cellulosic fiber and another separator, for example.

(121) As a material for the separator, one or more materials selected from the following can be used besides polyphenylene sulfide and solvent-spun regenerated cellulosic fiber: polypropylene sulfide, a fluorine-based polymer, cellulose, paper, nonwoven fabric, glass fiber, ceramics, synthetic fiber such as nylon (polyamide), vinylon (polyvinyl alcohol fiber), polyester, acrylic, polyolefin, or polyurethane, and the like.

(122) <<Electrolytic Solution>>

(123) The electrolytic solution contains an electrolyte and a solvent. Note that in this specification and the like, an electrolyte is referred to as a solute in some cases.

(124) As the solvent of the electrolytic solution, a material with carrier ion mobility is used. In particular, the solvent preferably has high heat resistance and low reactivity to a graphite negative electrode. In the power storage device of one embodiment of the present invention, a mixture of PC and EC is used as the solvent.

(125) As the solvent, an aprotic organic solvent is preferably used. For example, one of EC, PC,

butylene carbonate, γ -butyrolactone, γ -valerolactone, dimethyl sulfoxide, methyl diglyme, benzonitrile, and sulfolane can be used, or two or more of these solvents can be used in an appropriate combination in an appropriate ratio.

(126) When a gelled high-molecular material is used as the solvent of the electrolytic solution, safety against liquid leakage and the like is improved. Furthermore, the power storage device can be thinner and more lightweight. Typical examples of gelled high-molecular materials include a silicone gel, an acrylic gel, an acrylonitrile gel, a polyethylene oxide-based gel, a polypropylene oxide-based gel, a fluorine-based polymer gel, and the like.

(127) Alternatively, the use of one or more kinds of ionic liquids (room temperature molten salts) which have features of non-flammability and non-volatility as a solvent of the electrolytic solution can prevent the power storage device from exploding or catching fire even when the power storage device internally shorts out or the internal temperature increases owing to overcharging and others. Thus, the power storage device has improved safety.

(128) As the solute, a material that has carrier ion mobility and contains carrier ions can be used. In the case where carrier ions are lithium ions, the solute is a lithium salt. As a lithium salt, LiBETA, lithium bis(trifluoromethanesulfonyl)amide ($\text{Li}(\text{CF}_3\text{SO}_2)_2\text{N}$, abbreviation: LiTFSA), lithium bis(fluorosulfonyl)amide ($\text{Li}(\text{FSO}_2)_2\text{N}$, abbreviation: LiFSA), LiBF_4 , lithium bis(oxalato)borate ($\text{LiB}(\text{C}_2\text{O}_4)_2$, abbreviation: LiBOB), or the like, which has high heat resistance, is preferably used.

(129) In the power storage device, when a metal included in the positive electrode current collector is dissolved by a battery reaction between the electrolytic solution and the current collector, the capacity of the power storage device is decreased and the power storage device deteriorates. That is, the capacity is significantly decreased as charging and discharging are repeated through the cycle performance test of the power storage device, and the lifetime of the power storage device becomes short. Furthermore, when metal dissolution from the current collector at a connection portion between the lead and the current collector proceeds, disconnection might occur. In one embodiment of the present invention, a material which is unlikely to react with the current collector and thus is unlikely to cause the dissolution of the metal in the current collector is used for the solute material contained in the electrolytic solution.

(130) Examples of a metal in materials for the positive electrode current collector include aluminum and stainless steel. In one embodiment of the present invention, for a solute material used for the electrolytic solution, the solute that is unlikely to dissolve such a metal included in the positive electrode current collector is used. Specifically, LiBETA can be given as a lithium salt that can be used as the solute in one embodiment of the present invention.

(131) Therefore, in the power storage device of one embodiment of the present invention, the dissolution of the metal included in the positive electrode current collector into the electrolytic solution is inhibited, so that the deterioration of the positive electrode current collector is inhibited. In addition, the deposition of the metal on a surface of the negative electrode is inhibited, so that the capacity reduction is small, and the power storage device can have a favorable cycle lifetime.

(132) Other than the above electrolytes, one of lithium salts such as LiPF_6 , LiClO_4 , LiAsF_6 , LiAlCl_4 , LiSCN , LiBr , LiI , Li_2SO_4 , $\text{Li}_2\text{B}_{10}\text{Cl}_{10}$, $\text{Li}_2\text{B}_{12}\text{Cl}_{12}$, LiCF_3SO_3 , $\text{LiC}_4\text{F}_9\text{SO}_3$, $\text{LiC}(\text{CF}_3\text{SO}_2)_3$, $\text{LiC}(\text{C}_2\text{F}_5\text{SO}_2)_3$, $\text{LiN}(\text{C}_4\text{F}_9\text{SO}_2)_2$ (CF_3SO_2), and $\text{LiN}(\text{C}_2\text{F}_5\text{SO}_2)_2$ can be used, or two or more of these lithium salts can be used in an appropriate combination in an appropriate ratio.

(133) Although the case where carrier ions are lithium ions in the above electrolyte is described, carrier ions other than lithium ions can be used. When the carrier ions other than lithium ions are alkali metal ions or alkaline-earth metal ions, instead of lithium in the lithium salts, an alkali metal (e.g., sodium or potassium) or an alkaline-earth metal (e.g., calcium, strontium, barium, beryllium, or magnesium) may be used as the electrolyte.

(134) Furthermore, an additive such as VC, propane sultone (PS), tert-butylbenzene (TBB), fluoroethylene carbonate (FEC), or LiBOB may be added to the electrolytic solution. The concentration of such an additive in the whole solvent is, for example, higher than or equal to 0.1 wt % and lower than or equal to 5 wt %.

(135) With the use of the above solvent and the above electrolyte, an electrolytic solution of the power storage device of one embodiment of the present invention can be formed.

(136) <<Current Collector>>

(137) There is no particular limitation on the current collector as long as it has high conductivity without causing a significant chemical change in a power storage device. For example, the positive electrode current collector and the negative electrode current collector can each be formed using a metal such as stainless steel, gold, platinum, zinc, iron, nickel, copper, aluminum, titanium, tantalum, or manganese, an alloy thereof, sintered carbon, or the like. Alternatively, copper or stainless steel that is coated with carbon, nickel, titanium, or the like may be used. Alternatively, the current collectors can each be formed using an aluminum alloy to which an element that improves heat resistance, such as silicon, titanium, neodymium, scandium, or molybdenum, is added. Still alternatively, a metal element that forms silicide by reacting with silicon can be used to form the current collectors. Examples of the metal element that forms silicide by reacting with silicon include zirconium, titanium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum, tungsten, cobalt, and nickel.

(138) An irreversible reaction with an electrolytic solution is sometimes caused on surfaces of the positive electrode current collector and the negative electrode current collector. Thus, the positive electrode current collector and the negative electrode current collector preferably have low reactivity to an electrolytic solution.

(139) The positive electrode current collector and the negative electrode current collector can each have any of various shapes including a foil-like shape, a plate-like shape (sheet-like shape), a net-like shape, a cylindrical shape, a coil shape, a punching-metal shape, an expanded-metal shape, a porous shape, and a shape of non-woven fabric as appropriate. The positive electrode current collector and the negative electrode current collector may each be formed to have micro irregularities on the surface thereof in order to enhance adhesion to the active material layer. The positive electrode current collector and the negative electrode current collector each preferably have a thickness of 5 μm to 30 μm inclusive.

(140) An undercoat layer may be provided over part of a surface of the current collector. The undercoat layer is a coating layer provided to reduce contact resistance between the current collector and the active material layer or to improve adhesion between the current collector and the active material layer. Note that the undercoat layer is not necessarily formed over the entire surface of the current collector and may be partly formed to have an island-like shape. In addition, the undercoat layer may serve as an active material to have capacity. For the undercoat layer, a carbon material can be used, for example. Examples of the carbon material include graphite, carbon black such as acetylene black, and a carbon nanotube. Examples of the undercoat layer include a metal layer, a layer containing carbon and high molecular compounds, and a layer containing metal and high molecular compounds.

(141) <<Active Material Layer>>

(142) The active material layer includes the active material. An active material refers only to a material that is involved in insertion and extraction of ions that are carriers. In this specification and the like, a layer including an active material is referred to as an active material layer. The active material layer may include a conductive additive and a binder in addition to the active material.

(143) The positive electrode active material layer includes one or more kinds of positive electrode active materials. The negative electrode active material layer includes one or more kinds of negative electrode active materials.

(144) The positive electrode active material and the negative electrode active material have a

central role in battery reactions of a power storage device, and receive and release carrier ions. To increase the lifetime of the power storage device, the active materials preferably have a little capacity involved in irreversible battery reactions, and have high charge and discharge efficiency. (145) For the positive electrode active material, a material into and from which carrier ions such as lithium ions can be inserted and extracted can be used. Examples of a positive electrode active material include materials having an olivine crystal structure, a layered rock-salt crystal structure, a spinel crystal structure, and a NASICON crystal structure.

(146) As the positive electrode active material, a compound such as LiCoO_2 , LiNiO_2 , or LiMn_2O_4 , V_2O_5 , Cr_2O_5 , MnO , or LiFeO_2 can be used.

(147) As an example of a material having an olivine crystal structure, lithium-containing complex phosphate (LiMPO_4 (general formula) (M is one or more of Fe(II), Mn(II), Co(II), and Ni(II))) can be given. Typical examples of LiMPO_4 are compounds such as LiFePO_4 , LiNiPO_4 , LiCoPO_4 , LiMnPO_4 , $\text{LiFe}_a\text{Ni}_b\text{PO}_4$, $\text{LiFe}_a\text{CO}_b\text{PO}_4$, $\text{LiFe}_a\text{Mn}_b\text{PO}_4$, $\text{LiNi}_c\text{CO}_d\text{PO}_4$, $\text{LiNi}_c\text{Mn}_d\text{PO}_4$ ($a+b \leq 1$, $0 < a < 1$, and $0 < b < 1$), $\text{LiFe}_c\text{Ni}_d\text{Co}_e\text{PO}_4$, $\text{LiFe}_c\text{Ni}_d\text{Mn}_e\text{PO}_4$, $\text{LiNi}_c\text{Co}_d\text{Mn}_e\text{PO}_4$ ($c+d+e \leq 1$, $0 < c < 1$, $0 < d < 1$, and $0 < e < 1$), and $\text{LiFe}_f\text{Ni}_g\text{Co}_h\text{Mn}_i\text{PO}_4$ ($f+g+h+i \leq 1$, $0 < f < 1$, $0 < g < 1$, $0 < h < 1$, and $0 < i < 1$).

(148) For example, lithium iron phosphate (LiFePO_4) is preferable because it properly has properties necessary for the positive electrode active material, such as safety, stability, high capacity density, high potential, and the existence of lithium ions which can be extracted in initial oxidation (charging).

(149) Examples of a material with a layered rock-salt crystal structure include lithium cobalt oxide (LiCoO_2), LiNiO_2 , LiMnO_2 , Li_2MnO_3 , a NiCo-containing material (general formula: $\text{LiNi}_x\text{Co}_{1-x}\text{O}_2$ ($0 < x < 1$)) such as $\text{LiNi}_{0.8}\text{Co}_{0.2}\text{O}_2$, a NiMn-containing material (general formula: $\text{LiNi}_x\text{Mn}_{1-x}\text{O}_2$ ($0 < x < 1$)) such as $\text{LiNi}_{0.5}\text{Mn}_{0.5}\text{O}_2$, a NiMnCo-containing material (also referred to as NMC) (general formula: $\text{LiNi}_x\text{Mn}_y\text{Co}_{1-x-y}\text{O}_2$ ($x > 0$, $y > 0$, $x+y < 1$)) such as $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$. Moreover, $\text{Li}(\text{Ni}_{0.8}\text{Co}_{0.15}\text{Al}_{0.05})\text{O}_2$, $\text{Li}_2\text{MnO}_3\text{-LiMO}_2$ ($\text{M}=\text{Co}$, Ni , or Mn), and the like can be given as the examples.

(150) In particular, LiCoO_2 is preferable because it has advantages such as high capacity, higher stability in the air than that of LiNiO_2 , and higher thermal stability than that of LiNiO_2 .

(151) Examples of a material with a spinel crystal structure include LiMn_2O_4 , $\text{Li}_{1+x}\text{Mn}_{2-x}\text{O}_4$ ($0 < x < 2$), $\text{LiMn}_{2-x}\text{Al}_x\text{O}_4$ ($0 < x < 2$), and $\text{LiMn}_{1.5}\text{Ni}_{0.5}\text{O}_4$.

(152) It is preferred that a small amount of lithium nickel oxide (LiNiO_2 or $\text{LiNi}_{1-x}\text{M}_x\text{O}_2$ ($0 < x < 1$, $\text{M}=\text{Co}$, Al , or the like)) be added to a material with a spinel crystal structure that contains manganese, such as LiMn_2O_4 , in which case advantages such as inhibition of the dissolution of manganese and the decomposition of an electrolytic solution can be obtained.

(153) Alternatively, a lithium-containing complex silicate expressed by $\text{Li}_{2-j}\text{MSiO}_4$ (general formula) (M is one or more of Fe(II), Mn(II), Co(II), or Ni(II); $0 \leq j \leq 2$) may be used as the positive electrode active material. Typical examples of the general formula $\text{Li}_{2-j}\text{MSiO}_4$ are compounds such as $\text{Li}_{2-j}\text{FeSiO}_4$, $\text{Li}_{2-j}\text{NiSiO}_4$, $\text{Li}_{2-j}\text{CoSiO}_4$, $\text{Li}_{2-j}\text{MnSiO}_4$, $\text{Li}_{2-j}\text{Fe}_j\text{Ni}_{1-j}\text{SiO}_4$, $\text{Li}_{2-j}\text{Fe}_j\text{Co}_{1-j}\text{SiO}_4$, $\text{Li}_{2-j}\text{Fe}_j\text{Mn}_{1-j}\text{SiO}_4$, $\text{Li}_{2-j}\text{Ni}_k\text{Co}_{1-k}\text{SiO}_4$, $\text{Li}_{2-j}\text{Ni}_k\text{Mn}_{1-k}\text{SiO}_4$ ($k+1 \leq 1$, $0 < k < 1$, and $0 < 1 < 1$), $\text{Li}_{2-j}\text{Fe}_m\text{Ni}_n\text{Co}_q\text{SiO}_4$, $\text{Li}_{2-j}\text{Fe}_m\text{Ni}_n\text{Co}_q\text{SiO}_4$, $\text{Li}_{2-j}\text{Fe}_m\text{Ni}_n\text{Co}_q\text{SiO}_4$.

(2-j)Fe.sub.mNi.sub.nMn.sub.qSiO.sub.4, Li.sub.(2-j)Ni.sub.mCo.sub.nMn.sub.qSiO.sub.4 (m+n+q≤1, 0<m<1, 0<n<1, and 0<q<1), and Li.sub.

(2-j)Fe.sub.rNi.sub.sCo.sub.tMn.sub.uSiO.sub.4 (r+s+t+u≤1, 0<r<1, 0<s<1, 0<t<1, and 0<u<1).

(154) Still alternatively, a NASICON compound expressed by A.sub.xM.sub.2(XO.sub.4).sub.3 (general formula) (A=Li, Na, or Mg, M=Fe, Mn, Ti, V, Nb, or Al, X=S, P, Mo, W, As, or Si) can be used for the positive electrode active material. Examples of the NASICON compound are Fe.sub.2(MnO.sub.4).sub.3, Fe.sub.2(SO.sub.4).sub.3, and Li.sub.3Fe.sub.2(PO.sub.4).sub.3.

(155) Further alternatively, for example, a compound expressed by Li.sub.2MPO.sub.4F, Li.sub.2MP.sub.2O.sub.7, or Li.sub.5MO.sub.4 (general formula) (M=Fe or Mn), a perovskite fluoride such as FeF.sub.3, a metal chalcogenide (a sulfide, a selenide, or a telluride) such as TiS.sub.2 and MoS.sub.2, a lithium-containing material with an inverse spinel structure such as LiMVO.sub.4, a vanadium oxide (V.sub.2O.sub.5, V.sub.6O.sub.13, LiV.sub.3O.sub.8, LiVOPO.sub.4, or the like), a manganese oxide, or an organic sulfur compound can be used as the positive electrode active material.

(156) Further alternatively, any of the aforementioned materials may be combined to be used as the positive electrode active material. For example, a solid solution obtained by combining two or more of the above materials can be used as the positive electrode active material. For example, a solid solution of LiCo.sub.1/3Mn.sub.1/3Ni.sub.1/3O.sub.2 and Li.sub.2MnO.sub.3 can be used as the positive electrode active material.

(157) In the case where carrier ions are alkali metal ions other than lithium ions, or alkaline-earth metal ions, a compound containing carriers such as an alkali metal (e.g., sodium and potassium) or an alkaline-earth metal (e.g., calcium, strontium, barium, beryllium, and magnesium) instead of lithium of the lithium compound, the lithium-containing complex phosphate, or the lithium-containing complex silicate may be used as the positive electrode active material.

(158) The average diameter of primary particles of the positive electrode active material is preferably, for example, greater than or equal to 5 nm and less than or equal to 100 μm.

(159) For example, lithium-containing complex phosphate having an olivine crystal structure used for the positive electrode active material has a one-dimensional lithium diffusion path, so that lithium diffusion is slow. Thus, in the case of using lithium-containing complex phosphate having an olivine crystal structure, the average diameter of particles of the positive electrode active material is, for example, preferably greater than or equal to 5 nm and less than or equal to 1 μm so that the charge and discharge rate is increased. The specific surface area of the positive electrode active material is, for example, preferably greater than or equal to 10 m.sup.2/g and less than or equal to 50 m.sup.2/g.

(160) An active material having an olivine crystal structure is much less likely to be changed in the crystal structure by charging and discharging and has a more stable crystal structure than, for example, an active material having a layered rock-salt crystal structure. Thus, a positive electrode active material having an olivine crystal structure is stable against operation such as overcharging. The use of such a positive electrode active material allows fabrication of a highly safe power storage device.

(161) As the negative electrode active material, for example, a carbon-based material, an alloy-based material, or the like can be used.

(162) Examples of the carbon-based material include graphite, graphitizing carbon (soft carbon), non-graphitizing carbon (hard carbon), a carbon nanotube, graphene, carbon black, and the like. Examples of the graphite include artificial graphite such as meso-carbon microbeads (MCMB), coke-based artificial graphite, or pitch-based artificial graphite and natural graphite such as spherical natural graphite. In addition, examples of the shape of the graphite include a flaky shape and a spherical shape.

(163) Graphite has a low potential substantially equal to that of a lithium metal when lithium ions are intercalated into the graphite (while a lithium-graphite intercalation compound is formed). For

this reason, a lithium-ion secondary battery can have a high operating voltage. Graphite is preferred because of its advantages described above, such as relatively high capacity per unit volume, small volume expansion, low cost, and safety greater than that of a lithium metal.

(164) Here, a graphite material will be described. Graphite is a layered compound in which a plurality of graphene layers are stacked parallel to each other by van der Waals forces. A surface of the graphite material includes a plane parallel to the graphene layer (also referred to as a basal plane) and a plane where edges of the plurality of graphene layers are arranged (also referred to as an edge plane). In the basal plane, one surface of the outmost layer of the graphene layers composing graphite is exposed. In the edge plane, the edges of the plurality of graphene layers are exposed. In charging and discharging of a secondary battery, the edge plane of the graphite material serves as a main gate for lithium intercalation and deintercalation to and from the graphite material.

(165) In the case where graphite is used for the negative electrode active material, the contact between the exposed portion of the edge plane and the electrolytic solution containing PC might cause a side reaction between graphite and PC in charging and discharging. In spherical natural graphite used for the negative electrode active material included in the power storage device of one embodiment of the present invention, a layer having lower crystallinity than a graphite layer is formed in contact with the edge plane; thus, a side reaction between graphite and PC can be inhibited in some cases.

(166) For example, in the case where carrier ions are lithium ions, a material including at least one of Mg, Ca, Ga, Si, Al, Ge, Sn, Pb, As, Sb, Bi, Ag, Au, Zn, Cd, Hg, In, and the like can be used as the alloy-based material. Such elements have a higher capacity than carbon. In particular, silicon has a high theoretical capacity of 4200 mAh/g, and therefore, the capacity of the power storage device can be increased. Examples of an alloy-based material (compound-based material) using such elements include Mg.sub.2Si , Mg.sub.2Ge , Mg.sub.2Sn , SnS.sub.2 , V.sub.2Sn.sub.3 , FeSn.sub.2 , CoSn.sub.2 , Ni.sub.3Sn.sub.2 , Cu.sub.6Sn , Ag.sub.3Sn , Ag.sub.3Sb , Ni.sub.2MnSb , CeSb.sub.3 , LaSn.sub.3 , $\text{La.sub.3Co.sub.2Sn.sub.7}$, CoSb.sub.3 , InSb , and SbSn .

(167) Alternatively, for the negative electrode active material, an oxide such as SiO , SnO , SnO.sub.2 , titanium dioxide (TiO.sub.2), lithium titanium oxide ($\text{Li.sub.4Ti.sub.5O.sub.12}$), lithium-graphite intercalation compound (Li.sub.xC.sub.6), niobium pentoxide (Nb.sub.2O.sub.5), tungsten oxide (WO.sub.2), or molybdenum oxide (MoO.sub.2) can be used. Here, SiO is a compound containing silicon and oxygen. When the atomic ratio of silicon to oxygen is represented by $\alpha:\beta$, α preferably has an approximate value of β . Here, when α has an approximate value of β , an absolute value of the difference between α and β is preferably less than or equal to 20% of a value of β , more preferably less than or equal to 10% of a value of β .

(168) Still alternatively, for the negative electrode active material, $\text{Li.sub.3-xM.sub.xN}$ ($\text{M}=\text{Co}$, Ni , or Cu) with a Li.sub.3N structure, which is a nitride containing lithium and a transition metal, can be used. For example, $\text{Li.sub.2.6Co.sub.0.4N.sub.3}$ is preferable because of high charge and discharge capacity (900 mAh/g and 1890 mAh/cm³).

(169) When a nitride containing lithium and a transition metal is used, lithium ions are contained in the negative electrode active material and thus the negative electrode active material can be used in combination with a material for a positive electrode active material that does not contain lithium ions, such as V.sub.2O.sub.5 or Cr.sub.3O.sub.8 . In the case of using a material containing lithium ions as a positive electrode active material, the nitride containing lithium and a transition metal can be used for the negative electrode active material by extracting the lithium ions contained in the positive electrode active material in advance.

(170) Alternatively, a material that causes a conversion reaction can be used for the negative electrode active material; for example, a transition metal oxide that does not cause an alloy reaction with lithium, such as cobalt oxide (CoO), nickel oxide (NiO), and iron oxide (FeO), may be used. Other examples of the material which causes a conversion reaction include oxides such as Fe.sub.2O.sub.3 , CuO , Cu.sub.2O , RuO.sub.2 , and Cr.sub.2O.sub.3 , sulfides such as CoS.sub.0.89 ,

NiS, and CuS, nitrides such as Zn.sub.3N.sub.2, Cu.sub.3N, and Ge.sub.3N.sub.4, phosphides such as NiP.sub.2, FeP.sub.2, and CoP.sub.3, and fluorides such as FeF.sub.3 and BiF.sub.3.

(171) The average diameter of primary particles of the negative electrode active material is preferably, for example, greater than or equal to 5 nm and less than or equal to 100 μm .

(172) The positive electrode active material layer and the negative electrode active material layer may each include a conductive additive.

(173) Examples of the conductive additive include a carbon material, a metal material, and a conductive ceramic material. Alternatively, a fiber material may be used as the conductive additive. The content of the conductive additive in the active material layer is preferably greater than or equal to 1 wt % and less than or equal to 10 wt %, more preferably greater than or equal to 1 wt % and less than or equal to 5 wt %.

(174) A network for electric conduction can be formed in the electrode by the conductive additive. The conductive additive also allows maintaining of a path for electric conduction between the negative electrode active material particles. The addition of the conductive additive to the active material layer increases the electric conductivity of the active material layer.

(175) Examples of the conductive additive include natural graphite, artificial graphite such as mesocarbon microbeads, and carbon fiber. Examples of carbon fiber include mesophase pitch-based carbon fiber, isotropic pitch-based carbon fiber, carbon nanofiber, and carbon nanotube. Carbon nanotube can be formed by, for example, a vapor deposition method. Other examples of the conductive additive include carbon materials such as carbon black (e.g., acetylene black (AB)), graphite (black lead) particles, graphene, graphene oxide, and fullerene. Alternatively, metal powder or metal fibers of copper, nickel, aluminum, silver, gold, or the like, a conductive ceramic material, or the like can be used.

(176) Flaky graphene has an excellent electrical characteristic of high conductivity and excellent physical properties of high flexibility and high mechanical strength. Thus, the use of graphene as the conductive additive can increase contact points and the contact area of the active materials.

(177) Graphene is capable of making low-resistance surface contact and has extremely high conductivity even with a small thickness. Therefore, even a small amount of graphene can efficiently form a conductive path in an active material layer.

(178) In the case where an active material with a small average particle diameter (e.g., 1 μm or less) is used, the specific surface area of the active material is large and thus more conductive paths for the active material particles are needed. In such a case, it is particularly preferred that graphene with extremely high conductivity that can efficiently form a conductive path even in a small amount is used.

(179) The positive electrode active material layer and the negative electrode active material layer may each include a binder.

(180) In this specification, the binder has a function of binding or bonding the active materials and/or a function of binding or bonding the active material layer and the current collector. The binder is sometimes changed in state during fabrication of an electrode or a battery. For example, the binder can be at least one of a liquid, a solid, and a gel. The binder is sometimes changed from a monomer to a polymer during fabrication of an electrode or a battery.

(181) As the binder, for example, a water-soluble high molecular compound can be used. As the water-soluble high molecular compound, a polysaccharide or the like can be used. As the polysaccharide, a cellulose derivative such as carboxymethyl cellulose (CMC), methyl cellulose, ethyl cellulose, hydroxypropyl cellulose, diacetyl cellulose, or regenerated cellulose, starch, or the like can be used.

(182) As the binder, a rubber material such as styrene-butadiene rubber (SBR), styrene-isoprene-styrene rubber, acrylonitrile-butadiene rubber, butadiene rubber, fluororubber, or ethylene-propylene-diene copolymer can be used. Any of these rubber materials may be used in combination with the aforementioned water-soluble high molecular compound. Since these rubber materials

have rubber elasticity and easily expand and contract, it is possible to obtain a highly reliable electrode that is resistant to stress due to expansion and contraction of an active material by charging and discharging, bending of the electrode, or the like. On the other hand, the rubber materials have a hydrophobic group and thus are unlikely to be soluble in water in some cases. In such a case, particles are dispersed in an aqueous solution without being dissolved in water, so that increasing the viscosity of a composition containing a solvent used for the formation of the active material layer (also referred to as an electrode binder composition) up to the viscosity suitable for application might be difficult. A water-soluble high molecular compound having excellent viscosity modifying properties, such as a polysaccharide, can moderately increase the viscosity of the solution and can be uniformly dispersed together with a rubber material. Thus, a favorable electrode with high uniformity (e.g., an electrode with uniform electrode thickness or electrode resistance) can be obtained.

(183) Alternatively, as the binder, a material such as PVdF, polystyrene, poly(methyl acrylate), poly(methyl methacrylate) (PMMA), sodium polyacrylate, polyvinyl alcohol (PVA), polyethylene oxide (PEO), polypropylene oxide, polyimide, polyvinyl chloride, polytetrafluoroethylene, polyethylene, polypropylene, polyisobutylene, polyethylene terephthalate, nylon, polyacrylonitrile (PAN), ethylene-propylene-diene polymer, polyvinyl acetate, or nitrocellulose can be used.

(184) Two or more of the above materials may be used in combination for the binder.

(185) The content of the binder in the active material layer is preferably greater than or equal to 1 wt % and less than or equal to 10 wt %, more preferably greater than or equal to 2 wt % and less than or equal to 8 wt %, and still more preferably greater than or equal to 3 wt % and less than or equal to 5 wt %.

(186) <<Exterior Body>>

(187) It is preferred that the surface of the exterior body **509** that is in contact with the electrolytic solution **508**, i.e., the inner surface of the exterior body **509**, does not react with the electrolytic solution **508** significantly. When moisture enters the power storage device **500** from the outside, a reaction between a component of the electrolytic solution **508** or the like and water might occur. Thus, the exterior body **509** preferably has low moisture permeability.

(188) As the exterior body **509**, a film having a three-layer structure can be used, for example. In the three-layer structure, a highly flexible metal thin film of aluminum, stainless steel, copper, nickel, or the like is provided over a film formed using polyethylene, polypropylene, polycarbonate, ionomer, polyamide, or the like, and an insulating synthetic resin film of a polyamide-based resin, a polyester-based resin, or the like is provided as the outer surface of the exterior body over the metal thin film can be used. With such a three-layer structure, the passage of an electrolytic solution and a gas can be blocked and an insulating property and resistance to the electrolytic solution can be provided. The exterior body is folded inside in two, or two exterior bodies are stacked with the inner surfaces facing each other, in which case application of heat melts the materials on the overlapping inner surfaces to cause fusion bonding between the two exterior bodies. In this manner, a sealing structure can be formed.

(189) A portion where the sealing structure is formed by fusion bonding or the like of the exterior body is referred to as a sealing portion. In the case where the exterior body is folded inside in two, the sealing portion is formed in the place other than the fold, and a first region of the exterior body and a second region of the exterior body that overlaps with the first region are fusion-bonded, for example. In the case where two exterior bodies are stacked, the sealing portion is formed along the entire outer region by heat fusion bonding or the like.

(190) The power storage device **500** can be flexible by using the exterior body **509** with flexibility. When the power storage device **500** has flexibility, it can be used in an electronic device at least part of which is flexible, and the power storage device **500** can be bent as the electronic device changes its form.

(191) Note that in one embodiment of the present invention, a graphene compound can be used in a

component of the power storage device. As described later, when modification is performed, the structure and characteristics of a graphene compound can be selected from a wider range of alternatives. Thus, a preferable property can be exhibited in accordance with a component in which a graphene compound is to be used. Moreover, a graphene compound has high mechanical strength and therefore can be used in a component of a flexible power storage device. Graphene compounds will be described below.

(192) Graphene has carbon atoms arranged in one atomic layer. A π bond exists between the carbon atoms. Graphene including two or more and one hundred or less layers is referred to as multilayer graphene in some cases. The length in the longitudinal direction or the length of the major axis in a plane in each of graphene and multilayer graphene is greater than or equal to 50 nm and less than or equal to 100 μm or greater than or equal to 800 nm and less than or equal to 50 μm .

(193) In this specification and the like, a compound including graphene or multilayer graphene as a basic skeleton is referred to as a graphene compound. Graphene compounds include graphene and multilayer graphene.

(194) Graphene compounds will be detailed below.

(195) A graphene compound is, for example, a compound where graphene or multilayer graphene is modified with an atom other than carbon or an atomic group with an atom other than carbon. A graphene compound may be a compound where graphene or multilayer graphene is modified with an atomic group composed mainly of carbon, such as an alkyl group or alkylene. An atomic group that modifies graphene or multilayer graphene is referred to as a substituent, a functional group, a characteristic group, or the like in some cases. Modification in this specification and the like refers to introduction of an atom other than carbon, an atomic group with an atom other than carbon, or an atomic group composed mainly of carbon to graphene, multilayer graphene, a graphene compound, or graphene oxide (described later) by a substitution reaction, an addition reaction, or other reactions.

(196) Note that the surface and the rear surface of graphene may be modified with different atoms or atomic groups. In multilayer graphene, multiple layers may be modified with different atoms or atomic groups.

(197) An example of the above-described graphene modified with an atom or an atomic group is graphene or multilayer graphene that is modified with oxygen or a functional group containing oxygen. Examples of a functional group containing oxygen include an epoxy group, a carbonyl group such as a carboxyl group, and a hydroxyl group. A graphene compound modified with oxygen or a functional group containing oxygen is referred to as graphene oxide in some cases. In this specification, graphene oxides include multilayer graphene oxides.

(198) As an example of modification of graphene oxide, silylation of graphene oxide will be described. First, in a nitrogen atmosphere, graphene oxide is put in a container, n-butylamine (C.sub.4H.sub.9NH.sub.2) is added to the container, and stirring is performed for one hour with the temperature kept at 60° C. Then, toluene is added to the container, alkyltrichlorosilane is added thereto as a silylating agent, and stirring is performed in a nitrogen atmosphere for five hours with the temperature kept at 60° C. Then, toluene is further added to the container, and the resulting solution is suction-filtrated to give solid powder. The powder is dispersed in ethanol, and the resulting solution is suction-filtered to give solid powder. The powder is dispersed in acetone, and the resulting solution is suction-filtered to give solid powder. A liquid of the solid powder is vaporized to give silylated graphene oxide.

(199) The modification is not limited to silylation, and silylation is not limited to the above-described method. Furthermore, the modification is not limited to introduction of an atom or an atomic group of one kind, and the modification of two or more types may be performed to introduce atoms or atomic groups of two or more kinds. By introducing a given atomic group to a graphene compound, the physical property of the graphene compound can be changed. Therefore, by performing desirable modification in accordance with the use of a graphene compound, a

desired property of the graphene compound can be exhibited intentionally.

(200) A formation method example of graphene oxide will be described below. Graphene oxide can be obtained by oxidizing the aforementioned graphene or multilayer graphene. Alternatively, graphene oxide can be obtained by being separated from graphite oxide. Graphite oxide can be obtained by oxidizing graphite. The graphene oxide may further be modified with the above-mentioned atom or atomic group.

(201) A compound that can be obtained by reducing graphene oxide is referred to as reduced graphene oxide (RGO) in some cases. In RGO, in some cases, all oxygen atoms contained in the graphene oxide are not extracted and part of them remains in a state of oxygen or an atomic group containing oxygen that is bonded to carbon. In some cases, RGO includes a functional group, e.g., an epoxy group, a carbonyl group such as a carboxyl group, or a hydroxyl group.

(202) A graphene compound may have a sheet-like shape where a plurality of graphene compounds partly overlap with each other. Such a graphene compound is referred to as a graphene compound sheet in some cases. The graphene compound sheet has, for example, an area with a thickness larger than or equal to 0.33 nm and smaller than or equal to 10 mm, preferably larger than or equal to 0.34 nm and smaller than or equal to 10 μ m. The graphene compound sheet may be modified with an atom other than carbon, an atomic group containing an atom other than carbon, an atomic group composed mainly of carbon such as an alkyl group, or the like. A plurality of layers in the graphene compound sheet may be modified with different atoms or atomic groups.

(203) A graphene compound may have a five-membered ring composed of carbon atoms or a poly-membered ring that is a seven- or more-membered ring composed of carbon atoms, in addition to a six-membered ring composed of carbon atoms. In the neighborhood of a poly-membered ring which is a seven- or more-membered ring, a region through which a lithium ion can pass may be generated.

(204) Furthermore, a plurality of graphene compounds may be gathered to form a sheet-like shape, for example.

(205) A graphene compound has a planar shape, thereby enabling surface contact.

(206) In some cases, a graphene compound has high conductivity even when it is thin. The contact area between graphene compounds or between a graphene compound and an active material can be increased by surface contact. Thus, even with a small amount of a graphene compound per volume, a conductive path can be formed efficiently.

(207) In contrast, a graphene compound may also be used as an insulator. For example, a graphene compound sheet can be used as a sheet-like insulator. Graphene oxide, for example, has a more excellent insulation property than a graphene compound that is not oxidized, in some cases. A graphene compound modified with an atomic group may have an improved insulation property, depending on the type of the modifying atomic group.

(208) A graphene compound in this specification and the like may include a precursor of graphene. The precursor of graphene refers to a substance used to form graphene. The precursor of graphene may contain the above-described graphene oxide, graphite oxide, or the like.

(209) Graphene containing an alkali metal or an element other than carbon, such as oxygen, is referred to as a graphene analog in some cases. In this specification and the like, graphene compounds include graphene analogs.

(210) A graphene compound in this specification and the like may include an atom, an atomic group, and ions of them between the layers. The physical properties, such as electric conductivity and ionic conductivity, of a graphene compound sometimes change when an atom, an atomic group, and ions of them exist between layers of the compound. In addition, a distance between the layers is increased in some cases.

(211) A graphene compound has excellent electrical characteristics of high conductivity and excellent physical properties of high flexibility and high mechanical strength in some cases. A modified graphene compound can have extremely low conductivity and serve as an insulator

depending on the type of the modification. A graphene compound has a planar shape. A Graphene compound enables low-resistance surface contact.

(212) This embodiment can be combined with any of the other embodiments as appropriate.

Embodiment 2

(213) In this embodiment, electronic devices of embodiments of the present invention will be described with reference to FIG. 12A to 12C to FIGS. 15A to 15C.

(214) <Structural Example 1 of Smartwatch>

(215) FIG. 12A is a perspective view of a watch-type portable information terminal (also called a smartwatch) 700. The portable information terminal 700 includes a housing 701, a display panel 702, a clasp 703, bands 705A and 705B, and operation buttons 711 and 712.

(216) The display panel 702 mounted in the housing 701 doubling as a bezel includes a rectangular display region. The display region has a curved surface. The display panel 702 preferably has flexibility. Note that the display region may be non-rectangular.

(217) The bands 705A and 705B are connected to the housing 701. The clasp 703 is connected to the band 705A. The band 705A and the housing 701 are connected to each other with a pin such that they can pivot around the pin at a connection portion, for example. In a similar manner, the band 705B and the housing 701 are connected to each other and the band 705A and the clasp 703 are connected to each other.

(218) FIGS. 12B and 12C are perspective views of the band 705A and a power storage device 750, respectively. The band 705A includes the power storage device 750. As the power storage device 750, the power storage device 500 described in Embodiment 1 can be used, for example. The power storage device 750 is embedded in the band 705A, and part of the positive electrode lead 751 and part of the negative electrode lead 752 protrude from the band 705A (see FIG. 12B). The positive electrode lead 751 and the negative electrode lead 752 are electrically connected to the display panel 702. The surface of the power storage device 750 is covered with an exterior body 753 (see FIG. 12C). Note that the pin may function as an electrode. Specifically, the positive electrode lead 751 and the display panel 702 may be electrically connected to each other through the pin that connects the band 705A and the housing 701, and the negative electrode lead 752 and the display panel 702 may be electrically connected to each other through the pin. In that case, the structure of the connection portion between the band 705A and the housing 701 can be simplified.

(219) The power storage device 750 has flexibility. Specifically, a surface of the exterior body 753 preferably has projections and depressions formed by the embossing described in Embodiment 1. Furthermore, the power storage device 750 preferably has sliding planes of the power storage device 500 illustrated in FIGS. 4A and 4B.

(220) The band 705A can be formed so as to incorporate the power storage device 750. For example, the power storage device 750 is set in a mold that the outside shape of the band 705A fits and a material of the band 705A is poured in the mold and cured, so that the band 705A illustrated in FIG. 12B can be formed.

(221) In the case where a rubber material is used as the material of the band 705A, rubber is cured through heat treatment. For example, in the case where fluorine rubber is used as a rubber material, it is cured through heat treatment at 170° C. for 10 minutes. In the case where silicone rubber is used as a rubber material, it is cured through heat treatment at 150° C. for 10 minutes. The power storage device of one embodiment of the present invention has high heat resistance, which can inhibit breakage and degradation of the charge and discharge characteristics due to heat treatment performed when the power storage device and the rubber material are integrally formed.

(222) Examples of the material of the band 705A include fluorine rubber, silicone rubber, fluorosilicone rubber, and urethane rubber.

(223) Note that energization of the power storage device 750, including aging, is preferably performed after the power storage device 750 is formed to be incorporated in the band 705A. In other words, heat treatment is preferably performed on the power storage device 500 described in

Embodiment 1 before energization of the power storage device **500**. The heat treatment is preferably performed at 110° C. to 190° C. inclusive for a period of time suitable for vulcanization of the rubber material, for example, at 170° C. for 10 minutes. This can inhibit degradation of the charge and discharge characteristics of the power storage device **500** due to heat treatment.

(224) The portable information terminal **700** in FIG. **12A** can have a variety of functions such as a function of displaying a variety of data (e.g., a still image, a moving image, and a text image) on the display region, a touch panel function, a function of displaying a calendar, date, time, and the like, a function of controlling processing with a variety of software (programs), a wireless communication function, a function of being connected to a variety of computer networks with a wireless communication function, a function of transmitting and receiving a variety of data with a wireless communication function, and a function of reading out a program or data stored in a recording medium and displaying it on the display region.

(225) The housing **701** can include a speaker, a sensor (a sensor having a function of measuring force, displacement, position, speed, acceleration, angular velocity, rotational frequency, distance, light, liquid, magnetism, temperature, chemical substance, sound, time, hardness, electric field, current, voltage, electric power, radiation, flow rate, humidity, gradient, oscillation, odor, or infrared rays), a microphone, and the like. Note that the portable information terminal **700** can be manufactured using the light-emitting element for the display panel **702**.

(226) Although FIGS. **12A** to **12C** illustrate the example where the power storage device **750** is incorporated in the band **705A**, the power storage device **750** may be incorporated in the band **705B**. The band **705B** can be formed using a material similar to that of the band **705A**.

(227) The rubber material used for the band **705A** preferably has high chemical resistance. Specifically, the rubber material preferably has low reactivity to an electrolytic solution contained in the power storage device **750**.

(228) When the band **705A** is cracked or chipped despite of its high chemical resistance, a user of the portable information terminal **700** might touch the electrolytic solution that leaks from the power storage device **750**. In the case where the portable information terminal **700** has a function of detecting leakage of the electrolytic solution, the user can stop operation of the portable information terminal **700** and remove it as soon as the electrolytic solution leakage is detected. Consequently, the portable information terminal **700** can be highly safe.

(229) <Structural Example 2 of Smartwatch>

(230) FIG. **13A** is a perspective view of a band **735A** having a structure different form that of the band **705A** illustrated in FIG. **12B**. A housing **731** connected to the band **735A** includes a leakage detection circuit (not illustrated) having a function of detecting leakage of the electrolytic solution of the power storage device (see FIG. **12A**). Note that a perspective view of a portable information terminal **730** including the leakage detection circuit is similar to that of the portable information terminal **700**.

(231) The band **735A** includes a power storage device **760**. The power storage device **760** is embedded in the band **735A**, and part of the positive electrode lead **751**, part of the negative electrode lead **752**, part of a terminal **761**, and part of a terminal **762** protrude from the band **735A**. The positive electrode lead **751** and the negative electrode lead **752** are electrically connected to the display panel **702**. The terminal **761** and the terminal **762** are electrically connected to the above leakage detection circuit, for example.

(232) FIG. **13B** is a perspective view of the power storage device **760**. FIG. **13B** is an enlarged view of FIG. **13A** for clarification. The power storage device **760** is different from the power storage device **750** in FIG. **12C** in including the terminal **761**, terminal **762**, a wiring **771**, and a wiring **772**. The terminal **761** is electrically connected to the wiring **771**. The terminal **762** is electrically connected to the wiring **772**.

(233) Although the wiring **771** and the wiring **772** are indicated by different hatch patterns for clarification in FIG. **13B**, the wiring **771** and the wiring **772** are preferably formed using the same

material to achieve cost reduction. Although the terminal **761** and the wiring **771** are indicated by the same hatching pattern and the terminal **762** and the wiring **772** are indicated by the same hatching pattern, the terminal **761** and the wiring **771** may be formed using different materials and the terminal **762** and the wiring **772** may be formed using different materials.

(234) The wiring **771** and the wiring **772** are provided on a surface of the exterior body **753** with a predetermined gap therebetween (see FIG. **13B**). If the electrolytic solution leaks to a surface of the exterior body **753**, the wiring **771** and the wiring **772** are electrically connected to each other through the electrolytic solution, whereby the leakage detection circuit can detect leakage of the electrolytic solution.

(235) Although the wiring **771** and the wiring **772** each having a linear shape are provided in the direction of the long axis of the power storage device **760** in FIG. **13B**, one embodiment of the present invention is not limited thereto. For example, as illustrated in FIG. **13C**, the wiring **771** and the wiring **772** each having a comb-like shape may be provided with a gap therebetween so as to engage with each other.

(236) Although FIG. **13C** illustrates the example where the wirings **771** and **772** are provided only on the top surface of the exterior body **753**, the wirings **771** and **772** are preferably provided on the entire surface of the exterior body **753** as illustrated in FIG. **14A**. FIG. **14B** is a perspective view of the back surface of the power storage device **760** illustrated in FIG. **14A**.

(237) The wirings **771** and **772** each preferably have a small thickness and a small width, in which case the flexibility of the power storage device **760** can be ensured. For example, the power storage device **760** preferably includes a region in which the thickness of each of the wirings **771** and **772** is 5 μm to 500 μm inclusive. Furthermore, it is preferred that the gap between the wiring **771** and the wiring **772** be small and the width of each of the wiring **771** and the wiring **772** be small, in which case even a small amount of electrolytic solution leakage can be detected. For example, the power storage device **760** preferably includes a region in which the length of the gap between the wirings **771** and **772** is 0.5 mm and 20 mm inclusive. Furthermore, the power storage device **760** preferably includes a region in which the width of each of the wiring **771** and the wiring **772** is 0.5 mm and 5 mm inclusive. When the occupation area of the wirings **771** and **772** in the surface of the exterior body **753** is excessively small, the detection of electrolytic solution leakage for the entire surface of the exterior body **753** is not possible in some cases, whereas when the occupation area is excessively large, the flexibility of the power storage device **760** is low in some cases. In the power storage device **760**, the proportion of the surface area of the wirings **771** and **772** except side surfaces thereof (the surfaces in contact with the exterior body **753**) to the surface area of the exterior body **753** is preferably 5% to 50% inclusive.

(238) The wirings **771** and **772** preferably include a material having high ductility or high malleability. In particular, the use of a material having both high ductility and high malleability can suppress breakage of the wirings **771** and **772** due to curving of the power storage device **760**. Examples of the material having both high ductility and high malleability include a metal material such as gold, silver, platinum, iron, nickel, copper, aluminum, zinc, and tin and an alloy containing any of the metal materials.

(239) <<Leakage Detecting Method>>

(240) An example of a method for detecting electrolytic solution leakage in the portable information terminal **730** will be described below. FIG. **15A** is a block diagram of the configuration of the portable information terminal **730** when the electrolytic solution **736** leaks. In FIG. **15A**, lines with arrows indicate the directions in which a wired signal or a wireless signal is transmitted. Thus, components connected by the corresponding line are electrically connected to each other in some cases. Lines without an arrow indicate wirings, and components connected by the corresponding line are electrically connected to each other.

(241) The portable information terminal **730** includes a leakage detection circuit **732**, a power source **733**, an ammeter **734**, the wiring **771**, and the wiring **772** (see FIG. **15A**). The leakage

detection circuit **732**, the power source **733**, and the ammeter **734** are included in the housing **731**. The power source **733** and the ammeter **734** may be included in the leakage detection circuit **732**. The portable information terminal **730** also includes a functional circuit **739**. The functional circuit **739** includes the speaker, the sensor, the microphone, and the like. The functional circuit **739** is included in the housing **731**.

(242) The wirings **771** and **772** are electrically connected to the power source **733**, and a given voltage is applied between the wiring **771** and the wiring **772** (see FIG. **15A**). The on/off of the power source **733** is controlled by the leakage detection circuit **732**.

(243) FIG. **15B** is a flow chart showing the flow of detection of electrolytic solution leakage in the portable information terminal **730**. The method for detecting electrolytic solution leakage in the portable information terminal **730** includes the following four steps, for example.

(244) When the electrolytic solution **736** of the power storage device **760** leaks, the electrolytic solution **736** is attached to a surface of the exterior body **753** (see FIG. **15A** and **S1** in FIG. **15B**). The electrolytic solution **736** attached to the surface of the exterior body **753** comes in contact with the wiring **771** and the wiring **772**, whereby a current flows through the wiring **771** and the wiring **772** (see **S2** in FIG. **15B**). On detecting the current, the ammeter **734** connected in parallel to the wiring **772** outputs a detection signal to the leakage detection circuit **732** (see **S3** in FIG. **15B**). The leakage detection circuit **732** terminates the operation of the display panel **702** and/or the functional circuit **739** in response to the detection signal (see **S4** in FIG. **15B**).

(245) Although FIG. **15A** illustrates the example where the ammeter **734** is connected to the wiring **772**, the ammeter **734** may be connected to the wiring **771**. Furthermore, the power source **733** and the ammeter **734** may be included in the leakage detection circuit **732**, and the leakage detection circuit **732** may be electrically connected to the wirings **771** and **772** (see FIG. **15C**). In that case, the leakage detection circuit **732** has a function of applying a predetermined voltage to the wirings **771** and **772** and a function of detecting a current flowing through the wirings **771** and **772**.

(246) This embodiment can be combined with any of the other embodiments as appropriate.

Embodiment 3

(247) In this embodiment, flexible power storage devices that are embodiments of the present invention will be described with reference to FIGS. **16A** and **16B** to FIG. **23**. The power storage device of one embodiment of the present invention may have a curved shape. The power storage device of one embodiment of the present invention may be flexible and capable of being used while being curved and while being not curved.

Structural Example 1

(248) FIG. **16A** is a perspective view of a secondary battery **200** and FIG. **16B** is a top view of the secondary battery **200**.

(249) FIG. **17A** is a cross-sectional view along dashed-dotted line **C1-C2** in FIG. **16B**, and FIG. **17B** is a cross-sectional view along dashed-dotted line **C3-C4** in FIG. **16B**. Note that FIGS. **17A** and **17B** do not illustrate all components for clarity of the drawings.

(250) The secondary battery **200** includes a positive electrode **211**, a negative electrode **215**, and a separator **203**. The secondary battery **200** further includes a positive electrode lead **221**, a negative electrode lead **225**, and an exterior body **207**.

(251) The positive electrode **211** and the negative electrode **215** each include a current collector and an active material layer. The positive electrode **211** and the negative electrode **215** are provided such that the active material layers face each other with the separator **203** provided therebetween.

(252) One of the electrodes (the positive electrode **211** and the negative electrode **215**) of the secondary battery **200** that is positioned on the outer diameter side of a curved portion is preferably longer than the other electrode that is positioned on the inner diameter side of the curved portion, in the direction in which the electrode is curved. With such a structure, ends of the positive electrode **211** and those of the negative electrode **215** are aligned when the secondary battery **200** is curved with a certain curvature. That is, the entire region of the positive electrode active material layer

included in the positive electrode **211** can face the negative electrode active material layer included in the negative electrode **215**. Thus, positive electrode active materials included in the positive electrode **211** can efficiently contribute to a battery reaction. Therefore, the capacity of the secondary battery **200** per volume can be increased. Such a structure is particularly effective in a case where the curvature of the secondary battery **200** is fixed in using the secondary battery **200**. (253) The positive electrode lead **221** is electrically connected to a plurality of positive electrodes **211**. The negative electrode lead **225** is electrically connected to a plurality of negative electrodes **215**. The positive electrode lead **221** and the negative electrode lead **225** each include a sealing layer **220**.

(254) The exterior body **207** covers a plurality of positive electrodes **211**, a plurality of negative electrodes **215**, and a plurality of separators **203**. The secondary battery **200** includes an electrolytic solution (not shown) in a region covered with the exterior body **207**. Three sides of the exterior body **207** are bonded, whereby the secondary battery **200** is sealed.

(255) In FIGS. **17A** and **17B**, the separators **203** each having a strip-like shape are used and each pair of the positive electrode **211** and the negative electrode **215** sandwich the separator **203**; however, one embodiment of the present invention is not limited to this structure. One separator sheet may be folded in zigzag (or into a bellows shape) or wound so that the separator is positioned between the positive electrode and the negative electrode.

(256) An example of a method for fabricating the secondary battery **200** is illustrated in FIGS. **19A** to **19D**. FIG. **18** is a cross-sectional view along dashed-dotted line C1-C2 in FIG. **16B** of the case of employing this manufacturing method.

(257) First, the negative electrode **215** is positioned over the separator **203** (FIG. **19A**) such that the negative electrode active material layer of the negative electrode **215** overlaps with the separator **203**.

(258) Then, the separator **203** is folded to overlap with the negative electrode **215**. Next, the positive electrode **211** overlaps with the separator **203** (FIG. **19B**) such that the positive electrode active material layer of the positive electrode **211** overlaps with the separator **203** and the negative electrode active material layer. Note that in the case of using an electrode in which one surface of a current collector is provided with an active material layer, the positive electrode active material layer of the positive electrode **211** and the negative electrode active material layer of the negative electrode **215** are positioned to face each other with the separator **203** provided therebetween.

(259) In the case where the separator **203** is formed using a material that can be thermally welded, such as polypropylene, a region where the separator **203** overlaps with itself is thermally welded and then another electrode overlaps with the separator **203**, whereby the slippage of the electrode in the fabrication process can be suppressed. Specifically, a region which does not overlap with the negative electrode **215** or the positive electrode **211** and in which the separator **203** overlaps with itself, e.g., a region denoted as **203a** in FIG. **19B**, is preferably thermally welded.

(260) By repeating the above steps, the positive electrode **211** and the negative electrode **215** can overlap with each other with the separator **203** provided therebetween as illustrated in FIG. **19C**.

(261) Note that a plurality of positive electrodes **211** and a plurality of negative electrodes **215** may be placed to be alternately sandwiched by the separator **203** that is repeatedly folded in advance.

(262) Then, as illustrated in FIG. **19C**, a plurality of positive electrodes **211** and a plurality of negative electrodes **215** are covered with the separator **203**.

(263) Furthermore, the region where the separator **203** overlaps with itself, e.g., a region **203b** in FIG. **19D**, is thermally welded as illustrated in FIG. **19D**, whereby a plurality of positive electrodes **211** and a plurality of negative electrodes **215** are covered with and tied with the separator **203**.

(264) Note that a plurality of positive electrodes **211**, a plurality of negative electrodes **215**, and the separator **203** may be tied with a binding material.

(265) Since the positive electrodes **211** and the negative electrodes **215** are stacked in the above process, one separator **203** has a region sandwiched between a plurality of positive electrodes **211**

and a plurality of negative electrodes **215** and a region covering a plurality of positive electrodes **211** and a plurality of negative electrodes **215**.

(266) In other words, the separator **203** included in the secondary battery **200** in FIG. **18** and FIG. **19D** is a single separator which is partly folded. In the folded regions of the separator **203**, a plurality of positive electrodes **211** and a plurality of negative electrodes **215** are provided.

Structural Example 2

(267) FIG. **20A** is a perspective view of a secondary battery **250** and FIG. **20B** is a top view of the secondary battery **250**. Furthermore, FIG. **20C1** is a cross-sectional view of a first electrode assembly **230** and FIG. **20C2** is a cross-sectional view of a second electrode assembly **231**.

(268) The secondary battery **250** includes the first electrode assembly **230**, the second electrode assembly **231**, and the separator **203**. The secondary battery **250** further includes the positive electrode lead **221**, the negative electrode lead **225**, and the exterior body **207**.

(269) As illustrated in FIG. **20C1**, in the first electrode assembly **230**, a positive electrode **211a**, the separator **203**, a negative electrode **215a**, the separator **203**, and the positive electrode **211a** are stacked in this order. The positive electrode **211a** and the negative electrode **215a** each include active material layers on opposite surfaces of a current collector.

(270) As illustrated in FIG. **20C2**, in the second electrode assembly **231**, a negative electrode **215a**, the separator **203**, the positive electrode **211a**, the separator **203**, and the negative electrode **215a** are stacked in this order. The positive electrode **211a** and the negative electrode **215a** each include active material layers on opposite surfaces of a current collector.

(271) In other words, in each of the first electrode assembly **230** and the second electrode assembly **231**, the positive electrode and the negative electrode are provided such that the active material layers face each other with the separator **203** provided therebetween.

(272) The positive electrode lead **221** is electrically connected to a plurality of positive electrodes **211**. The negative electrode lead **225** is electrically connected to a plurality of negative electrodes **215**. The positive electrode lead **221** and the negative electrode lead **225** each include the sealing layer **220**.

(273) FIG. **21** is an example of a cross-sectional view along dashed-dotted line D1-D2 in FIG. **20B**. Note that FIG. **21** does not illustrate all components for clarity of the drawings.

(274) As illustrated in FIG. **21**, the secondary battery **250** has a structure in which a plurality of first electrode assemblies **230** and a plurality of second electrode assemblies **231** are covered with the wound separator **203**.

(275) The exterior body **207** covers a plurality of first electrode assemblies **230**, a plurality of second electrode assemblies **231**, and the separator **203**. The secondary battery **200** includes an electrolytic solution (not shown) in a region covered with the exterior body **207**. Three sides of the exterior body **207** are bonded, whereby the secondary battery **200** is sealed.

(276) An example of a method for fabricating the secondary battery **250** is illustrated in FIGS. **22A** to **22D**.

(277) First, the first electrode assembly **230** is positioned over the separator **203** (FIG. **22A**).

(278) Then, the separator **203** is folded to overlap with the first electrode assembly **230**. After that, two second electrode assemblies **231** are positioned over and under the first electrode assembly **230** with the separator **203** positioned between each of the second electrode assemblies **231** and the first electrode assembly **230** (FIG. **22B**).

(279) Then, the separator **203** is wound to cover the two second electrode assemblies **231**. Moreover, two first electrode assemblies **230** are positioned over and under the two second electrode assemblies **231** with the separator **203** positioned between each of the first electrode assemblies **230** and each of the second electrode assemblies **231** (FIG. **22C**).

(280) Then, the separator **203** is wound to cover the two first electrode assemblies **230** (FIG. **22D**).

(281) Since a plurality of first electrode assemblies **230** and a plurality of second electrode assemblies **231** are stacked in the above process, these electrode assemblies are each positioned

surrounded with the spirally wound separator **203**.

(282) Note that the outermost electrode preferably does not include an active material layer on the outer side.

(283) Although FIGS. **20C1** and **20C2** each illustrate a structure in which the electrode assembly includes three electrodes and two separators, one embodiment of the present invention is not limited to this structure. The electrode assembly may include four or more electrodes and three or more separators. A larger number of electrodes lead to higher capacity of the secondary battery **250**. Alternatively, the electrode assembly may include two electrodes and one separator. A smaller number of electrodes enable higher resistance of the secondary battery against bending. Although FIG. **21** illustrates the structure in which the secondary battery **250** includes three first electrode assemblies **230** and two second electrode assemblies **231**, one embodiment of the present invention is not limited to this structure. The number of the electrode assemblies may be increased. A larger number of electrode assemblies lead to higher capacity of the secondary battery **250**. The number of the electrode assemblies may be decreased. A smaller number of electrode assemblies enable higher resistance of the secondary battery against bending.

(284) FIG. **23** illustrates another example of a cross-sectional view along dashed-dotted line D1-D2 in FIG. **20B**. As illustrated in FIG. **23**, the separator **203** may be folded into a bellows shape so that the separator **203** is positioned between the first electrode assembly **230** and the second electrode assembly **231**.

(285) This embodiment can be combined with any of the other embodiments as appropriate.
Embodiment 4

(286) In this embodiment, application examples of the power storage device of one embodiment of the present invention will be described with reference to FIGS. **24A** to **24F** to FIGS. **28A** and **28B**.

(287) The power storage device of one embodiment of the present invention can be used for an electronic device or a lighting device, for example. The power storage device of one embodiment of the present invention has excellent charge and discharge characteristics. Therefore, the electronic device or the lighting device can be used for a long time by a single charge. Moreover, since a decrease in capacity with an increasing number of charge and discharge cycles is inhibited, the time between charges is unlikely to be reduced by repetitive charge. Furthermore, the power storage device of one embodiment of the present invention exhibits excellent charge and discharge characteristics and high long-term reliability and is highly safe at a wide range of temperature including high temperatures, so that the safety and reliability of an electronic device or a lighting device can be improved.

(288) Examples of electronic devices include a television set (also referred to as a television or a television receiver), a monitor of a computer or the like, a digital camera, a digital video camera, a digital photo frame, a mobile phone (also referred to as a mobile phone device), a portable game machine, a portable information terminal, an audio reproducing device, a large game machine such as a pinball machine, and the like.

(289) Since the power storage device of one embodiment of the present invention is flexible, the power storage device or an electronic device or a lighting device using the power storage device can be incorporated along a curved inside/outside wall surface of a house or a building or a curved interior/exterior surface of a motor vehicle.

(290) FIG. **24A** illustrates an example of a mobile phone. A mobile phone **7400** is provided with a display portion **7402** incorporated in a housing **7401**, an operation button **7403**, an external connection port **7404**, a speaker **7405**, a microphone **7406**, and the like. Note that the mobile phone **7400** includes a power storage device **7407**.

(291) FIG. **24B** illustrates the mobile phone **7400** in the state of being bent. When the whole mobile phone **7400** is bent by the external force, the power storage device **7407** included in the mobile phone **7400** is also bent. The power storage device **7407** is a thin power storage device. The power storage device **7407** is fixed in a state of being bent. FIG. **24C** illustrates the power storage

device **7407** in the state of being bent

(292) FIG. **24D** illustrates an example of a bangle display device. A portable display device **7100** includes a housing **7101**, a display portion **7102**, an operation button **7103**, and a power storage device **7104**. FIG. **24E** illustrates the bent power storage device **7104**.

(293) FIG. **24F** illustrates an example of a watch-type portable information terminal. A portable information terminal **7200** includes a housing **7201**, a display portion **7202**, a band **7203**, a buckle **7204**, an operation button **7205**, an input output terminal **7206**, and the like.

(294) The portable information terminal **7200** is capable of executing a variety of applications such as mobile phone calls, e-mailing, viewing and editing text, music reproduction, Internet communication, and a computer game.

(295) The display surface of the display portion **7202** is curved, and images can be displayed on the curved display surface. In addition, the display portion **7202** includes a touch sensor, and operation can be performed by touching the screen with a finger, a stylus, or the like. For example, by touching an icon **7207** displayed on the display portion **7202**, application can be started.

(296) With the operation button **7205**, a variety of functions such as time setting, power ON/OFF, ON/OFF of wireless communication, setting and cancellation of silent mode, and setting and cancellation of power saving mode can be performed. For example, the functions of the operation button **7205** can be set freely by the operating system incorporated in the portable information terminal **7200**.

(297) Furthermore, the portable information terminal **7200** can employ near field communication, which is a communication method based on an existing communication standard. In that case, for example, mutual communication between the portable information terminal **7200** and a headset capable of wireless communication can be performed, and thus hands-free calling is possible.

(298) Moreover, the portable information terminal **7200** includes the input output terminal **7206**, and data can be directly transmitted to and received from another information terminal via a connector. In addition, charging via the input output terminal **7206** is possible. Note that the charging operation may be performed by wireless power feeding without using the input output terminal **7206**.

(299) The display portion **7202** of the portable information terminal **7200** is provided with the power storage device of one embodiment of the present invention. For example, the power storage device **7104** illustrated in FIG. **24E** that is in the state of being curved can be provided in the housing **7201**. Alternatively, the power storage device **7104** illustrated in FIG. **24E** can be provided in the band **7203** such that it can be curved.

(300) FIG. **25A** illustrates an example of a wrist-worn activity meter. The activity meter **7250** includes a housing **7251**, the band **7203**, the buckle **7204**, and the like. Furthermore, the housing **7251** incorporates a wireless communication device, a pulse sensor, an acceleration sensor, a temperature sensor, and the like. The activity meter **7250** has a function of acquiring data such as pulse variation and the amount of activity of the user with the pulse sensor and the acceleration sensor and sending the data to an external portable information terminal by the wireless communication device. Furthermore, the activity meter **7250** may have a function of measuring calorie consumption and calorie intake of the user, a function of measuring the number of steps taken, a function of measuring a sleeping condition, or the like. Note that the activity meter **7250** may be provided with a display portion for displaying data acquired by the above function.

(301) The activity meter **7250** includes the power storage device of one embodiment of the present invention. For example, the power storage device **7104** illustrated in FIG. **24E** that is in the state of being curved can be provided in the housing **7201**. Alternatively, the power storage device **7104** illustrated in FIG. **24E** can be provided in the band **7203** such that it can be curved.

(302) FIG. **25B** illustrates an example of an armband display device. A display device **7300** includes a display portion **7304** and the power storage device of one embodiment of the present invention. The display device **7300** can include a touch sensor in the display portion **7304** and can

serve as a portable information terminal.

(303) The display surface of the display portion **7304** is bent, and images can be displayed on the bent display surface. A display state of the display device **7300** can be changed by, for example, near field communication, which is a communication method based on an existing communication standard.

(304) The display device **7300** includes an input output terminal, and data can be directly transmitted to and received from another information terminal via a connector. In addition, charging via the input output terminal is possible. Note that the charging operation may be performed by wireless power feeding without using the input output terminal.

(305) FIG. **25C** illustrates an example of a glasses-type display device. A display device **7350** includes lenses **7351**, a frame **7352**, and the like. Furthermore, a projection portion (not illustrated) that projects an image or video on the lenses **7351** is provided in the frame **7352** or in contact with the frame **7352**. The display device **7350** has a function of displaying an image **7351A** on the entire lenses **7351** in the direction in which the user can see the image **7351A**. Alternatively, the display device **7350** has a function of displaying an image **7351B** on part of the lenses **7351** in the direction in which the user can see the image **7351B**.

(306) The display device **7350** includes the power storage device of one embodiment of the present invention. FIG. **25D** is an enlarged view of an edge portion **7355** of the frame **7352**. The edge portion **7355** can be formed using a rubber material such as fluorine rubber or silicone rubber. The power storage device **7360** of one embodiment of the present invention is embedded in the edge portion **7355**, and the positive electrode lead **7361** and the negative electrode lead **7362** protrude from the edge portion **7355**. The positive electrode lead **7361** and the negative electrode lead **7362** are electrically connected to a wiring provided in the frame **7352** and connected to a projection portion or the like. Note that the edge portion **7355** can be formed so as to incorporate the power storage device **7360** as in Embodiment 2.

(307) The edge portion **7355** and the power storage device **7360** have flexibility. Thus, the display device **7350** can be worn so as to be in close contact with the user along with the shape of the head of the user.

(308) FIGS. **26A** and **26B** illustrate an example of a tablet terminal that can be folded in half. A tablet terminal **9600** illustrated in FIGS. **26A** and **26B** includes a pair of housings **9630**, a movable portion **9640** connecting the pair of housings **9630**, a display portion **9631a**, a display portion **9631b**, a display mode changing switch **9626**, a power switch **9627**, a power saving mode changing switch **9625**, a fastener **9629**, and an operation switch **9628**. FIG. **26A** illustrates the tablet terminal **9600** that is opened, and FIG. **26B** illustrates the tablet terminal **9600** that is closed.

(309) The tablet terminal **9600** includes a power storage unit **9635** inside the housings **9630**. The power storage unit **9635** is provided across the housings **9630**, passing through the movable portion **9640**.

(310) Part of the display portion **9631a** can be a touch panel region **9632a**, and data can be input by touching operation keys **9638** that are displayed. Note that FIG. **26A** shows, as an example, that half of the area of the display portion **9631a** has only a display function and the other half of the area has a touch panel function. However, the structure of the display portion **9631a** is not limited to this, and all the area of the display portion **9631a** may have a touch panel function. For example, all the area of the display portion **9631a** can display a keyboard and serve as a touch panel while the display portion **9631b** can be used as a display screen.

(311) As in the display portion **9631a**, part of the display portion **9631b** can be a touch panel region **9632b**. When a keyboard display switching button **9639** displayed on the touch panel is touched with a finger, a stylus, or the like, a keyboard can be displayed on the display portion **9631b**.

(312) Touch input can be performed in the touch panel region **9632a** and the touch panel region **9632b** at the same time.

(313) The display mode changing switch **9626** allows switching between a landscape mode and a

portrait mode, color display and black-and-white display, and the like. The power saving mode changing switch **9625** can control display luminance in accordance with the amount of external light in use of the tablet terminal **9600**, which is measured with an optical sensor incorporated in the tablet terminal **9600**. In addition to the optical sensor, other detecting devices such as sensors for determining inclination, such as a gyroscope or an acceleration sensor, may be incorporated in the tablet terminal.

(314) Although the display portion **9631a** and the display portion **9631b** have the same area in FIG. **26A**, one embodiment of the present invention is not limited to this example. The display portion **9631a** and the display portion **9631b** may have different areas or different display quality. For example, one of the display portions **9631a** and **9631b** may display higher definition images than the other.

(315) The tablet terminal is closed in FIG. **26B**. The tablet terminal includes the housings **9630**, a solar cell **9633**, and a charge and discharge control circuit **9634** including a DC-DC converter **9636**. The power storage device of one embodiment of the present invention is used as the power storage unit **9635**.

(316) The tablet terminal **9600** can be folded such that the housings **9630** overlap with each other when not in use. Thus, the display portions **9631a** and **9631b** can be protected, which increases the durability of the tablet terminal **9600**. In addition, the power storage unit **9635** of one embodiment of the present invention has flexibility and can be repeatedly bent without a significant decrease in charge and discharge capacity. Thus, a highly reliable tablet terminal can be provided.

(317) The tablet terminal illustrated in FIGS. **26A** and **26B** can also have a function of displaying various kinds of data (e.g., a still image, a moving image, and a text image) on the display portion, a function of displaying a calendar, a date, or the time on the display portion, a touch-input function of operating or editing data displayed on the display portion by touch input, a function of controlling processing by various kinds of software (programs), and the like.

(318) The solar cell **9633**, which is attached on the surface of the tablet terminal, supplies electric power to a touch panel, a display portion, an image signal processing portion, and the like. Note that the solar cell **9633** can be provided on one surface or opposite surfaces of the housing **9630** and the power storage unit **9635** can be charged efficiently. The use of a lithium-ion battery as the power storage unit **9635** brings an advantage such as reduction in size.

(319) The structure and operation of the charge and discharge control circuit **9634** illustrated in FIG. **26B** will be described with reference to a block diagram in FIG. **26C**. The solar cell **9633**, the power storage unit **9635**, the DC-DC converter **9636**, a converter **9637**, switches SW1 to SW3, and the display portion **9631** are illustrated in FIG. **26C**, and the power storage unit **9635**, the DC-DC converter **9636**, the converter **9637**, and the switches SW1 to SW3 correspond to the charge and discharge control circuit **9634** in FIG. **26B**.

(320) First, an example of operation when electric power is generated by the solar cell **9633** using external light will be described. The voltage of electric power generated by the solar cell is raised or lowered by the DC-DC converter **9636** to a voltage for charging the power storage unit **9635**. When the display portion **9631** is operated with the electric power from the solar cell **9633**, the switch SW1 is turned on and the voltage of the electric power is raised or lowered by the converter **9637** to a voltage needed for operating the display portion **9631**. When display on the display portion **9631** is not performed, the switch SW1 is turned off and the switch SW2 is turned on, so that the power storage unit **9635** can be charged.

(321) Note that the solar cell **9633** is described as an example of a power generation means; however, one embodiment of the present invention is not limited to this example. The power storage unit **9635** may be charged using another power generation means such as a piezoelectric element or a thermoelectric conversion element (Peltier element). For example, the power storage unit **9635** may be charged with a non-contact power transmission module capable of performing charging by transmitting and receiving electric power wirelessly (without contact), or any of the

other charge means used in combination.

(322) FIG. 27 illustrates other examples of electronic devices. In FIG. 27, a display device **8000** is an example of an electronic device including a power storage device **8004** of one embodiment of the present invention. Specifically, the display device **8000** corresponds to a display device for TV broadcast reception and includes a housing **8001**, a display portion **8002**, speaker portions **8003**, and the power storage device **8004**. The power storage device **8004** of one embodiment of the present invention is provided in the housing **8001**. The display device **8000** can receive electric power from a commercial power supply. Alternatively, the display device **8000** can use electric power stored in the power storage device **8004**. Thus, the display device **8000** can be operated with the use of the power storage device **8004** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(323) A semiconductor display device such as a liquid crystal display device, a light-emitting device in which a light-emitting element such as an organic EL element is provided in each pixel, an electrophoresis display device, a digital micromirror device (DMD), a plasma display panel (PDP), or a field emission display (FED) can be used for the display portion **8002**.

(324) Note that the display device includes, in its category, all of information display devices for personal computers, advertisement displays, and the like besides TV broadcast reception.

(325) In FIG. 27, an installation lighting device **8100** is an example of an electronic device including a power storage device **8103** of one embodiment of the present invention. Specifically, the lighting device **8100** includes a housing **8101**, a light source **8102**, and the power storage device **8103**. Although FIG. 27 illustrates the case where the power storage device **8103** is provided in a ceiling **8104** on which the housing **8101** and the light source **8102** are installed, the power storage device **8103** may be provided in the housing **8101**. The lighting device **8100** can receive electric power from a commercial power supply. Alternatively, the lighting device **8100** can use electric power stored in the power storage device **8103**. Thus, the lighting device **8100** can be operated with the use of power storage device **8103** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(326) Note that although the installation lighting device **8100** provided in the ceiling **8104** is illustrated in FIG. 27 as an example, the power storage device of one embodiment of the present invention can be used in an installation lighting device provided in, for example, a wall **8105**, a floor **8106**, a window **8107**, or the like other than the ceiling **8104**. Alternatively, the power storage device of one embodiment of the present invention can be used in a tabletop lighting device or the like.

(327) As the light source **8102**, an artificial light source which emits light artificially by using electric power can be used. Specifically, an incandescent lamp, a discharge lamp such as a fluorescent lamp, and light-emitting elements such as an LED and an organic EL element are given as examples of the artificial light source.

(328) In FIG. 27, an air conditioner including an indoor unit **8200** and an outdoor unit **8204** is an example of an electronic device including a power storage device **8203** of one embodiment of the present invention. Specifically, the indoor unit **8200** includes a housing **8201**, an air outlet **8202**, and the power storage device **8203**. Although FIG. 27 illustrates the case where the power storage device **8203** is provided in the indoor unit **8200**, the power storage device **8203** may be provided in the outdoor unit **8204**. Alternatively, the power storage devices **8203** may be provided in both the indoor unit **8200** and the outdoor unit **8204**. The air conditioner can receive electric power from a commercial power supply. Alternatively, the air conditioner can use electric power stored in the power storage device **8203**. Particularly in the case where the power storage devices **8203** are provided in both the indoor unit **8200** and the outdoor unit **8204**, the air conditioner can be operated with the use of the power storage device **8203** of one embodiment of the present invention

as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(329) Note that although the split-type air conditioner including the indoor unit and the outdoor unit is illustrated in FIG. 27 as an example, the power storage device of one embodiment of the present invention can be used in an air conditioner in which the functions of an indoor unit and an outdoor unit are integrated in one housing.

(330) In FIG. 27, an electric refrigerator-freezer **8300** is an example of an electronic device including a power storage device **8304** of one embodiment of the present invention. Specifically, the electric refrigerator-freezer **8300** includes a housing **8301**, a door for a refrigerator **8302**, a door for a freezer **8303**, and the power storage device **8304**. The power storage device **8304** is provided in the housing **8301** in FIG. 27. The electric refrigerator-freezer **8300** can receive electric power from a commercial power supply. Alternatively, the electric refrigerator-freezer **8300** can use electric power stored in the power storage device **8304**. Thus, the electric refrigerator-freezer **8300** can be operated with the use of the power storage device **8304** of one embodiment of the present invention as an uninterruptible power supply even when electric power cannot be supplied from a commercial power supply due to power failure or the like.

(331) Note that a high-frequency heating apparatus such as a microwave oven and an electronic device such as an electric rice cooker require high power in a short time. The tripping of a breaker of a commercial power supply in use of an electronic device can be prevented by using the power storage device of one embodiment of the present invention as an auxiliary power supply for supplying electric power which cannot be supplied enough by a commercial power supply.

(332) In addition, in a time period when electronic devices are not used, particularly when the proportion of the amount of electric power which is actually used to the total amount of electric power which can be supplied from a commercial power supply source (such a proportion referred to as a usage rate of electric power) is low, electric power can be stored in the power storage device, whereby the usage rate of electric power can be reduced in a time period when the electronic devices are used. For example, in the case of the electric refrigerator-freezer **8300**, electric power can be stored in the power storage device **8304** in night time when the temperature is low and the door for a refrigerator **8302** and the door for a freezer **8303** are not often opened or closed. On the other hand, in daytime when the temperature is high and the door for a refrigerator **8302** and the door for a freezer **8303** are frequently opened and closed, the power storage device **8304** is used as an auxiliary power supply; thus, the usage rate of electric power in daytime can be reduced.

(333) Furthermore, the power storage device of one embodiment of the present invention can be provided in a vehicle.

(334) The use of power storage devices in vehicles enables production of next-generation clean energy vehicles such as hybrid electric vehicles (HEVs), electric vehicles (EVs), and plug-in hybrid electric vehicles (PHEVs).

(335) FIGS. 28A and 28B each illustrate an example of a vehicle using one embodiment of the present invention. An automobile **8400** illustrated in FIG. 28A is an electric vehicle that runs on the power of an electric motor. Alternatively, the automobile **8400** is a hybrid electric vehicle capable of driving appropriately using either the electric motor or the engine. One embodiment of the present invention can provide a high-mileage vehicle. The automobile **8400** includes the power storage device. The power storage device is used not only for driving the electric motor, but also for supplying electric power to a light-emitting device such as a headlight **8401** or a room light (not illustrated).

(336) The power storage device can also supply electric power to a display device of a speedometer, a tachometer, or the like included in the automobile **8400**. Furthermore, the power storage device can supply electric power to a semiconductor device included in the automobile **8400**, such as a navigation system.

(337) FIG. 28B illustrates an automobile 8500 including the power storage device. The automobile 8500 can be charged when the power storage device is supplied with electric power through external charging equipment by a plug-in system, a contactless power feeding system, or the like. In FIG. 28B, a power storage device included in the automobile 8500 is charged with the use of a ground-based charging apparatus 8021 through a cable 8022. In charging, a given method such as CHAdeMO (registered trademark) or Combined Charging System may be employed as a charging method, the standard of a connector, or the like as appropriate. The ground-based charging apparatus 8021 may be a charging station provided in a commerce facility or a power source in a house. For example, with the use of a plug-in technique, the power storage device included in the automobile 8500 can be charged by being supplied with electric power from outside. The charging can be performed by converting AC electric power into DC electric power through a converter such as an AC-DC converter.

(338) Furthermore, although not illustrated, the vehicle may include a power receiving device so that it can be charged by being supplied with electric power from an above-ground power transmitting device in a contactless manner. In the case of the contactless power feeding system, by fitting a power transmitting device in a road or an exterior wall, charging can be performed not only when the electric vehicle is stopped but also when driven. In addition, the contactless power feeding system may be utilized to perform transmission and reception of electric power between vehicles. Furthermore, a solar cell may be provided in the exterior of the automobile to charge the power storage device when the automobile stops or moves. To supply electric power in such a contactless manner, an electromagnetic induction method or a magnetic resonance method can be used.

(339) According to one embodiment of the present invention, the power storage device can have improved cycle characteristics and reliability. Furthermore, according to one embodiment of the present invention, the power storage device itself can be made more compact and lightweight as a result of improved characteristics of the power storage device. The compact and lightweight power storage device contributes to a reduction in the weight of a vehicle, and thus increases the driving distance. Furthermore, the power storage device included in the vehicle can be used as a power source for supplying electric power to products other than the vehicle. In such a case, the use of a commercial power source can be avoided at peak time of electric power demand.

(340) This embodiment can be combined with any of the other embodiments as appropriate.

Example 1

(341) In this example, evaluation results of the characteristics of the power storage device of one embodiment of the present invention that was fabricated will be described.

(342) In this example, the power storage device 500 illustrated in FIG. 1A was fabricated.

(343) In this example, the following 8 samples formed using one embodiment of the present invention were used in total: Samples A1, A2, B1, B2, C1, C2, D1, and D2.

(344) The samples fabricated in this example each include one positive electrode in which a positive electrode active material layer is provided on one surface of a positive electrode current collector and one negative electrode in which a negative electrode active material layer is provided on one surface of a negative electrode current collector. In other words, the samples in this example each include one positive electrode active material layer and one negative electrode active material layer.

(345) First, methods for fabricating the electrodes will be described.

(346) [Fabricating Method for Negative Electrode]

(347) The same fabricating method was used to form the negative electrodes of all the samples in this example.

(348) Spherical natural graphite having a specific surface area of 6.3 m²/g and an average particle size of 15 μm (CGB-15 manufactured by Nippon Graphite Industries, Co., Ltd.) was used as a negative electrode active material. For a binder, sodium carboxymethyl cellulose (CMC-Na)

and SBR were used. The polymerization degree of CMC-Na that was used was higher than or equal to 600 and lower than or equal to 800, and the viscosity of a 1 wt % CMC-Na aqueous solution was in the range from 300 mPa·s to 500 mPa·s. The compounding ratio of graphite:CMC-Na:SBR was set to 97:1:1.5 (wt %).

(349) First, CMC-Na powder and an active material were mixed and then kneaded with a mixer, so that a first mixture was obtained.

(350) Subsequently, a small amount of water was added to the first mixture and kneading was performed, so that a second mixture was obtained. Here, “kneading” means “mixing something with a high viscosity”.

(351) Then, water was further added and the mixture was kneaded with a mixer, so that a third mixture was obtained.

(352) Then, a 50 wt % SBR aqueous dispersion liquid was added to the third mixture, and mixing was performed with a mixer. After that, the obtained mixture was degassed under a reduced pressure, so that a slurry was obtained.

(353) Subsequently, the slurry was applied to a negative electrode current collector with the use of a continuous coater. An 18- μ m-thick rolled copper foil was used as the negative electrode current collector. The coating speed was set to 0.75 m/min.

(354) Then, the solvent in the slurry applied to the negative electrode current collector was vaporized in a drying furnace. Vaporization treatment was performed at 50° C. in an air atmosphere for 120 seconds and then further performed at 80° C. in the air atmosphere for 120 seconds. After that, further vaporization treatment was performed at 100° C. under a reduced pressure (−100 KPa) for 10 hours.

(355) Through the above steps, the negative electrode active material layer was formed on one surface of the negative electrode current collector, so that the negative electrode was fabricated.

(356) [Fabrication Method for Positive Electrode]

(357) The same fabrication method was used to fabricate the positive electrodes of all the samples in this example.

(358) As each positive electrode active material, LiCoO_2 with a specific surface area of 0.21 m²/g and an average particle size of 10 μ m was used. As each binder, polyvinylidene fluoride (PVdF) was used. As each conductive additive, acetylene black was used. The compounding ratio of LiCoO_2 :acetylene black:PVdF was set to 90:5:5 (wt %).

(359) First, acetylene black and PVdF were mixed in a mixer, so that a first mixture was obtained.

(360) Next, the active material was added to the first mixture, so that a second mixture was obtained.

(361) After that, a solvent N-methyl-2-pyrrolidone (NMP) was added to the second mixture and mixing was performed with a mixer. Through the above steps, a slurry was formed.

(362) Then, mixing was performed with a large-sized mixer.

(363) Subsequently, the slurry was applied to a positive electrode current collector with the use of a continuous coater. A 20- μ m-thick aluminum current collector was used as the positive electrode current collector. The coating speed was set to 0.2 m/min.

(364) Then, the solvent in the slurry applied to the positive electrode current collector was vaporized in a drying furnace. Solvent vaporization treatment was performed at 70° C. in an air atmosphere for 7.5 minutes and then further performed at 90° C. in the air atmosphere for 7.5 minutes.

(365) After that, heat treatment was performed in a reduced-pressure atmosphere (at a gauge pressure of −100 kPa) at 170° C. for 10 hours. Subsequently, the positive electrode active material layer was pressed by a roll press method so as to be consolidated.

(366) Through the above steps, the positive electrode active material layer was formed on one surface of the positive electrode current collector, so that the positive electrode was fabricated.

(367) Table 1 lists the averages of the active material loadings, the thicknesses, and the densities of

each of the positive electrode active material layers and the negative electrode active material layers that were formed. The values shown in this specification are the averages of measurement values of each of the electrodes used in fabricating the samples. Note that when the active material layers were formed on opposite surfaces of the current collector, the values are the averages of the active material loadings, the thicknesses, and the densities of the active material layer on one surface of the current collector.

(368) TABLE-US-00001 TABLE 1 Sample Sample Sample Sample A1 A2 B1 B2 Positive Load 2 19.8 19.8 19.8 19.8 electrode (mg/cm.sup.2) Thickness 82 80 79 78 (μm) Density 2.42 2.48 2.50 2.54 (g/cc) Negative Load 10.2 10.2 10.3 10.3 electrode (mg/cm.sup.2) Thickness 108 107 111 110 (μm) Density 0.94 0.95 0.92 0.93 (g/cc) Sample Sample Sample Sample C1 C2 D1 D2 Positive Load 19.8 19.8 19.0 19.9 electrode (mg/cm.sup.2) Thickness 81 81 84 75 (μm) Density 2.40 2.40 2.26 2.65 (g/cc) Negative Load 10.2 10.2 10.1 10.4 electrode (mg/cm.sup.2) Thickness 108 107 108 111 (μm) Density 0.94 0.95 0.93 0.93 (g/cc)

(369) In electrolytic solutions, a solvent in which EC and PC are mixed at a volume ratio of 1:1 was used, and various kinds of solutes and additives were used as in Table 2. In each of Samples A1 and A2 (hereinafter, the composition of the electrolytic solutions of these samples is referred to as Condition A), 1 mol/l of LiTFSa was used as a solute of the electrolytic solution, and 1 wt % of VC and 2 wt % of LiFSA were used as additives. In each of Samples B1 and B2 (hereinafter, the composition of the electrolytic solutions of these samples is referred to as Condition B), 1 mol/l of LiFSA was used as a solute of the electrolytic solution, and 1 wt % of VC was used as an additive. In each of Samples C1 and C2 (hereinafter, the composition of the electrolytic solutions of these samples is referred to as Condition C), 1 mol/l of LiBETA was used as a solute of the electrolytic solution, and 1 wt % of VC was used as an additive. In each of Samples D1 and D2 (hereinafter, the composition of the electrolytic solutions of these samples is referred to as Condition D), 1 mol/l of LiBETA was used as a solute of the electrolytic solution, and 1 wt % of PS was used as an additive. In each sample of Condition A, LiFSA was used as the additive, whereas in each sample of Condition B, LiFSA was used as the solute.

(370) TABLE-US-00002 TABLE 2 Sample A1, A2 Sample B1, B2 Sample C1, C2 Sample D1, D2 Electrolytic Solvent EC:PC = 1:1 (v/v) solution Solute LiTFSa 1 mol/l LiFSA 1 mol/l LiBETA 1 mol/l LiBETA 1 mol/l Additive 1 VC 1 wt % PS 1 wt % Additive 2 LiFSA 2 wt % —

(371) As each separator, a stack of two 46-μm-thick separators using polyphenylene sulfide (hereinafter also referred to as PPS separators) was used.

(372) As an exterior body, an aluminum film with opposite surfaces covered with a resin layer was used.

(373) Next, fabrication methods for the samples will be described.

(374) First, a positive electrode, a negative electrode, and a separator were cut. The size of the positive electrode is 20.49 cm.sup.2, and the size of the negative electrode is 23.84 cm.sup.2.

(375) Then, the positive electrode active material and the negative electrode active material in tab regions were removed to expose the current collectors.

(376) After that, the positive electrode and the negative electrode were stacked with the separator therebetween. At this time, the positive electrode and the negative electrode were stacked such that the positive electrode active material layer and the negative electrode active material layer faced each other.

(377) Then, leads were attached to the positive electrode and the negative electrode by ultrasonic welding.

(378) Then, facing parts of two of four sides of the exterior body were bonded to each other by heating.

(379) After that, sealing layers provided for the leads were positioned so as to overlap with a sealing layer of the exterior body, and bonding was performed by heating. At this time, facing parts of a side of the exterior body except a side used for introduction of an electrolytic solution were

bonded to each other.

(380) Next, heat treatment for drying the exterior body and the positive electrode, the separator, and the negative electrode wrapped by the exterior body was performed in a reduced-pressure atmosphere (at a gauge pressure of -100 kPa) at 80° C. for 10 hours.

(381) Subsequently, in an argon gas atmosphere, an approximately $600\text{ }\mu\text{l}$ of electrolytic solution was introduced from one side of the exterior body that was not sealed. After that, the one side of the exterior body was sealed by heating in a reduced-pressure atmosphere (at a gauge pressure of -60 kPa). Through the above steps, each thin storage battery was fabricated.

(382) Next, heat treatment was performed on Samples A2, B2, C2, and D2. Assuming that each sample and fluorine rubber are integrally formed as in Embodiment 2, heat treatment was performed in an atmospheric pressure atmosphere at 170° C. for 15 minutes. Specifically, the temperature of a thermostatic bath was raised to approximately 170° C., each sample was put in the thermostatic bath, and after 15 minutes, the sample was taken out. Expansion accompanying the heat treatment did not occur in the exterior body of each sample.

(383) Through the above steps, the samples were fabricated.

(384) Next, the charge and discharge characteristics at 25° C. of the samples in this example were measured. The measurement was performed with a charge-discharge measuring instrument (produced by TOYO SYSTEM Co., LTD.). Constant current-constant voltage charging was performed until the voltage reached an upper voltage limit of 4.3 V, and constant voltage discharging was performed until the voltage reached a lower voltage limit of 2.5 V. The charging and discharging were performed at a rate of 0.1 C, and a 10-minute break was taken after the charging. Note that two charge and discharge cycles were performed.

(385) Here, a charge rate and a discharge rate will be described. A charge rate of 1 C means a current value at which a cell with a capacity of X (Ah) is charged at a constant current such that charging is terminated in exactly 1 hour. When $1\text{ C}=I$ (A), a charge rate of 0.2 C means $I/5$ (A), i.e., a current value at which charging is terminated in exactly 5 hours. Similarly, a discharge rate of 1 C means a current value at which a cell with a capacity of X (Ah) is discharged at a constant current such that discharging is terminated in exactly 1 hour. A discharge rate of 0.2 C means $I/5$ (A), i.e., a current value at which discharging is terminated in exactly 5 hours. Note that the rates were calculated using 170 mAh/g , which is capacity obtained when the upper charging voltage limit of $\text{LiCoO}_{2.2}$ serving as the positive electrode active material, is 4.3 V, as a reference.

(386) FIG. 29A shows charge and discharge curves of Sample A1. FIG. 29B shows charge and discharge curves of Sample A2. FIG. 29C shows charge and discharge curves of Sample B1. FIG. 29D shows charge and discharge curves of Sample B2. FIG. 30A shows charge and discharge curves of Sample C1. FIG. 30B shows charge and discharge curves of Sample C2. FIG. 30C shows charge and discharge curves of Sample D1. FIG. 30D shows charge and discharge curves of Sample D2. In FIGS. 29A to 29D and FIGS. 30A to 30D, the horizontal axis represents capacity (mAh/g), and the vertical axis represents voltage (V).

(387) As shown in FIGS. 29A and 29C, abnormal conditions occurred in the first charging of Samples A1, A2, B1, and B2, and the characteristics of Samples A1, A2, B1, and B2 were noticeably degraded in the first discharging. In the second discharging, the characteristics were further degraded. This suggests that LiTFSA and LiFSA , which are solutes of the electrolytic solutions, corrode aluminum of the positive electrode current collectors in the state where the potentials of the positive electrodes are high. Similar abnormal conditions occurred in the samples of Conditions A and B subjected to heat treatment (see FIGS. 29B and 29D).

(388) In contrast, as shown in FIGS. 30A and 30C, the first charging and the second charging were normally performed in Samples C1, C2, D1, and D2, and they have favorable charge and discharge characteristics. These results indicate that even in charging and discharging at a charging voltage of 4.3 V, corrosion of the positive electrode current collectors in the power storage devices using LiBETA as the solutes was inhibited and thus the power storage devices stably operated. As shown

in FIGS. 30B and 30D, decreases in the capacities of the samples of Conditions C and D subjected to heat treatment are small, and the samples have normal charge and discharge characteristics and high heat resistance. Table 3 shows the discharge capacity retention rates of the samples of Conditions C and D that are subjected to heat treatment. The discharge capacity retention rates were calculated using respective discharge capacities of the samples in the second cycle.

(389) TABLE-US-00003 TABLE 3 Capacity Capacity Capacity obtained obtained retention ratio without heat with heat obtained by treatment treatment heating (mAh/g) (mAh/g) (%) Condition C 126.7 (C1) 111.9 (C2) 88.3 Condition D 129.0 (D1) 118.6 (D2) 91.9

(390) FIGS. 30B and 30D and Table 3 indicate that the power storage devices using the electrolytic solution of Condition D have the highest heat resistance and the highest battery capacity.

Example 2

(391) In this example, results obtained by performing experiments to examine the state of a surface of spherical natural graphite used for the negative electrode active material included in the power storage device of one embodiment of the present invention will be described.

(392) [Cross-Sectional TEM Observation]

(393) Spherical natural graphite powder was sliced by a focused ion beam (FIB) method and taken out as a sample. The sample was observed with a cross-sectional transmission electron microscope (TEM) (H-9000NAR manufactured by Hitachi High-Technologies Corporation) at an acceleration voltage of 200 kV. FIGS. 31A to 31C show obtained TEM images. FIGS. 31B and 31C are enlarged TEM images showing a region 900 including the vicinity of an edge plane and a region 901 including the vicinity of a basal plane in FIG. 31A, respectively. Note that a minute edge presumably exists even in a plane seen as the basal plane in the cross-sectional TEM observation.

(394) The spherical natural graphite has a structure in which a graphite layer is folded (see FIG. 31A). As shown in FIGS. 31B and 31C, a coating layer 912 having lower crystallinity than graphite layers 911 arranged regularly is located outward from the graphite layers 911 (as the outermost surface layer of the spherical natural graphite) both in the vicinity of the edge plane and in the vicinity of the basal plane of the spherical natural graphite.

(395) [Raman Spectroscopy]

(396) Next, analysis results of Raman spectra by Raman spectroscopy will be described. For the analysis, two-point measurement was performed on spherical natural graphite powder with the use of a Raman microscope (LabRAM manufactured by HORIBA, Ltd.). Note that the wavelength of laser light used for the Raman analysis is 532 nm.

(397) FIG. 32 shows analysis results of Raman spectra of the spherical natural graphite powder. In FIG. 32, the D band (the peak at around 1360 cm.^{sup.}-1 of the Raman spectra) showing crystallinity disorder of graphite is clearly observed. Table 4 lists the intensity ratios (R values) of the D band to the G band (the peak at around 1580 cm.^{sup.}-1 of the Raman spectra). Since the D band is clearly observed, the R values are not small, specifically, 0.28 and 0.38. The R values, which are not small, may have a relation with the fact that the layer having reduced crystallinity on the surface of the spherical natural graphite is observed as shown in FIGS. 31B and 31C.

(398) TABLE-US-00004 TABLE 4 R value (D/G ratio) Point 1 0.38 Point 2 0.28

(399) Such a layer having low crystallinity on the outermost surface of a graphite particle, which can be observed with a TEM or by Raman spectroscopy as in this example, may be able to inhibit PC intercalation between graphite layers.

Example 3

(400) In this example, evaluation results of the characteristics of the power storage device of one embodiment of the present invention that was fabricated will be described.

(401) In this example, the power storage device 500 illustrated in FIG. 1A was fabricated.

(402) In this example, the following two samples formed using one embodiment of the present invention were used in total: Samples E1 and E2.

(403) The samples fabricated in this example each include one positive electrode in which a

positive electrode active material layer is provided on one surface of a positive electrode current collector and one negative electrode in which a negative electrode active material layer is provided on one surface of a negative electrode current collector. In other words, the samples in this example each include one positive electrode active material layer and one negative electrode active material layer.

(404) First, methods for fabricating the electrodes will be described.

(405) [Fabricating Method for Negative Electrode]

(406) The same fabricating method was used to form the negative electrodes of all the samples in this example.

(407) Spherical natural graphite having a specific surface area of 6.3 m²/g and an average particle size of 15 μm (CGB-15 manufactured by Nippon Graphite Industries, Co., Ltd.) was used as a negative electrode active material. For a binder, sodium carboxymethyl cellulose (CMC-Na) and SBR were used. The polymerization degree of CMC-Na that was used was higher than or equal to 600 and lower than or equal to 800, and the viscosity of a 1 wt % CMC-Na aqueous solution was in the range from 300 mPa·s to 500 mPa·s. The compounding ratio of graphite:CMC-Na:SBR was set to 97:1.5:1.5 (wt %).

(408) First, CMC-Na powder and an active material were mixed and then kneaded with a mixer, so that a first mixture was obtained.

(409) Subsequently, a small amount of water was added to the first mixture and kneading was performed, so that a second mixture was obtained. Here, “kneading” means “mixing something with a high viscosity”.

(410) Then, water was further added and the mixture was kneaded with a mixer, so that a third mixture was obtained.

(411) Then, a 50 wt % SBR aqueous dispersion liquid was added to the third mixture, and mixing was performed with a mixer. After that, the obtained mixture was degassed under a reduced pressure, so that a slurry was obtained.

(412) Subsequently, the slurry was applied to a negative electrode current collector with the use of a continuous coater. An 18-μm-thick rolled copper foil was used as the negative electrode current collector. The coating speed was set to 0.75 m/min.

(413) Then, the solvent in the slurry applied to the negative electrode current collector was vaporized in a drying furnace. Vaporization treatment was performed at 50° C. in an air atmosphere for 120 seconds and then further performed at 80° C. in the air atmosphere for 120 seconds. After that, further vaporization treatment was performed at 100° C. under a reduced pressure (−100 KPa) for 10 hours.

(414) Through the above steps, the negative electrode active material layer was formed on opposite surfaces of the negative electrode current collector, so that the negative electrode was fabricated.

(415) [Fabrication Method for Positive Electrode]

(416) The same fabrication method was used to fabricate the positive electrodes of all the samples in this example.

(417) As each positive electrode active material, LiCoO₂ with an average particle size of 6 μm was used. As each binder, polyvinylidene fluoride (PVdF) was used. As each conductive additive, acetylene black was used. The compounding ratio of LiCoO₂:acetylene black:PVdF was set to 95:3:2 (wt %).

(418) First, acetylene black and PVdF were mixed in a mixer, so that a first mixture was obtained.

(419) Next, the active material was added to the first mixture, so that a second mixture was obtained.

(420) After that, a solvent N-methyl-2-pyrrolidone (NMP) was added to the second mixture and mixing was performed with a mixer. Through the above steps, a slurry was formed.

(421) Then, mixing was performed with a large-sized mixer.

(422) Subsequently, the slurry was applied to a positive electrode current collector with the use of a

continuous coater. A 20- μm -thick aluminum current collector was used as the positive electrode current collector. The coating speed was set to 0.2 m/min.

(423) Then, the solvent in the slurry applied to the positive electrode current collector was vaporized in a drying furnace. Solvent vaporization treatment was performed at 70° C. in an air atmosphere for 7.5 minutes and then further performed at 90° C. in the air atmosphere for 7.5 minutes.

(424) After that, heat treatment was performed in a reduced-pressure atmosphere (at a gauge pressure of -100 kPa) at 170° C. for 10 hours. Subsequently, the positive electrode active material layer was pressed by a roll press method so as to be consolidated.

(425) Through the above steps, the positive electrode active material layer was formed on one surface of the positive electrode current collector, so that the positive electrode was fabricated.

(426) Table 5 lists the averages of the active material loadings, the thicknesses, and the densities of each of the positive electrode active material layers and the negative electrode active material layers that were formed. The values shown in this specification are the averages of measurement values of each of the electrodes used in fabricating the samples. Note that when the active material layers were formed on opposite surfaces of the current collector, the values are the averages of the active material loadings, the thicknesses, and the densities of the active material layer on one surface of the current collector.

(427) TABLE-US-00005

	Sample E1	Sample E2
Positive Load (mg/cm. ^{sup.2})	19.1	21.4
Thickness (μm)	61	69
Density (g/cc)	3.14	3.10
Negative Load (mg/cm. ^{sup.2})	10.3	10.4
Thickness (μm)	113	113
Density (g/cc)	0.92	0.92

(428) In each electrolytic solution, a solvent in which EC and PC are mixed at a volume ratio of 1:1 was used, 1 mol/l of LiBETA was used as a solute, and 1 wt % of PS was used as an additive. Table 6 lists the condition of the electrolytic solution. The condition of the electrolytic solution for Samples E1 and E2 is similar to Condition D in Example 1.

(429) TABLE-US-00006

	Sample E1, E2
Electrolytic Solvent	EC:PC 1:1 (v/v) solution
Solute	LiBETA 1 mol/l
Additive 1	PS 1 wt %
Additive 2	—

(430) As each separator, a stack of two 46- μm -thick separators using solvent-spun regenerated cellulosic fiber was used.

(431) As an exterior body, an aluminum film with opposite surfaces covered with a resin layer was used.

(432) Next, fabrication methods for the samples will be described.

(433) First, a positive electrode, a negative electrode, and a separator were cut. The size of the positive electrode is 20.49 cm.^{sup.2}, and the size of the negative electrode is 23.84 cm.^{sup.2}. Then, the positive electrode active material and the negative electrode active material in tab regions were removed to expose the current collectors.

(434) After that, the positive electrode and the negative electrode were stacked with the separator therebetween. At this time, the positive electrode and the negative electrode were stacked such that the positive electrode active material layer and the negative electrode active material layer faced each other.

(435) Then, leads were attached to the positive electrode and the negative electrode by ultrasonic welding.

(436) Then, the stack of the positive electrode and the negative electrode was wrapped in a sheet using polyphenylene sulfide in order to prevent the positive electrode or the negative electrode from coming in contact with an aluminum layer of the exterior body when the aluminum layer is exposed by heat treatment performed on the battery; accordingly, a short circuit can be prevented. Then, facing parts of two of four sides of the exterior body were bonded to each other by heating.

(437) After that, sealing layers provided for the leads were positioned so as to overlap with a sealing layer of the exterior body, and bonding was performed by heating. At this time, facing parts of a side of the exterior body except a side used for introduction of an electrolytic solution were

bonded to each other.

(438) Next, heat treatment for drying the exterior body and the positive electrode, the separator, and the negative electrode wrapped by the exterior body was performed in a reduced-pressure atmosphere (at a gauge pressure of -100 kPa) at 80° C. for 10 hours.

(439) Subsequently, in an argon gas atmosphere, an approximately $600\text{ }\mu\text{l}$ of electrolytic solution was introduced from one side of the exterior body that was not sealed. After that, the one side of the exterior body was sealed by heating in a reduced-pressure atmosphere (at a gauge pressure of -100 kPa). Through the above steps, each thin power storage device was fabricated.

(440) Next, heat treatment was performed on Sample E2. Assuming that the sample and fluorine rubber are integrally formed as in Embodiment 2, heat treatment was performed in an atmospheric pressure atmosphere at 170° C. for 15 minutes. Specifically, the temperature of a thermostatic bath was raised to approximately 170° C., the sample was put in the thermostatic bath, and after 15 minutes, the sample was taken out. Expansion accompanying the heat treatment did not occur in the exterior body of the sample.

(441) Through the above steps, the samples were fabricated.

(442) Next, the charge and discharge characteristics at 25° C. of the samples in this example were measured. The measurement was performed with a charge-discharge measuring instrument (produced by TOYO SYSTEM Co., LTD.). Constant current-constant voltage charging was performed until the voltage reached an upper voltage limit of 4.3 V, and constant voltage discharging was performed until the voltage reached a lower voltage limit of 2.5 V. The charging and discharging were performed at a rate of 0.1 C, and a 10-minute break was taken after the charging. Note that two charge and discharge cycles were performed.

(443) FIG. 33A shows charge and discharge curves of Sample E1. FIG. 33B shows charge and discharge curves of Sample E2. In FIGS. 33A and 33B, the horizontal axis represents capacity (mAh/g), and the vertical axis represents voltage (V).

(444) As shown in FIGS. 33A and 33B, the first charging and the second charging were normally performed in Samples E1 and E2, and they have favorable charge and discharge characteristics. Furthermore, the results shown in FIG. 33B indicate that a decrease in the capacity of even the sample subjected to heat treatment is small, and the sample has normal charge and discharge characteristics and high heat resistance.

(445) This application is based on Japanese Patent Application serial no. 2015-240755 filed with Japan Patent Office on Dec. 10, 2015, the entire contents of which are hereby incorporated by reference.

Claims

1. A power storage device comprising: a positive electrode; a positive electrode lead electrically connected to the positive electrode; a negative electrode; a negative electrode lead electrically connected to the negative electrode; a separator; an electrolytic solution; an exterior body; and a rubber material sealing the exterior body, wherein the positive electrode, the negative electrode, the separator and the electrolytic solution are sealed in the exterior body, wherein a part of the positive electrode lead and a part of the negative electrode lead protrude from the rubber material, wherein the exterior body comprises a plurality of projections and a plurality of depressions formed at regular intervals in a long axis direction of the power storage device, wherein one of the plurality of projections and one of the plurality of depressions are formed so as to extend in a short axis direction of the power storage device, wherein the positive electrode comprises a positive electrode active material layer and a positive electrode current collector, wherein the negative electrode comprises a negative electrode active material layer and a negative electrode current collector, wherein the separator is located between the positive electrode and the negative electrode, wherein the separator comprises polyphenylene sulfide or solvent-spun regenerated cellulosic fiber, wherein

the electrolytic solution comprises a solute and three or more kinds of solvents, and further comprises propane sultone as an additive, wherein the solute comprises lithium bis(pentafluoroethanesulfonyl)amide, wherein the three or more kinds of solvents comprise propylene carbonate and ethylene carbonate, and wherein propylene carbonate is the highest proportion in the electrolytic solution as a solvent except ethylene carbonate.

2. The power storage device according to claim 1, wherein the negative electrode active material layer comprises graphite.
 3. The power storage device according to claim 2, wherein the negative electrode active material layer comprises spherical natural graphite, wherein the spherical natural graphite comprises a first region and a second region, wherein the first region covers the second region, and wherein the first region has lower crystallinity than the second region.
 4. The power storage device according to claim 1, wherein the positive electrode active material layer comprises LiCoO_2 .
 5. The power storage device according to claim 1, wherein the positive electrode current collector comprises aluminum or stainless steel.
 6. An electronic device comprising: the power storage device according to claim 2; a display panel; and a housing, wherein the power storage device has flexibility, wherein the power storage device is electrically connected to the display panel, wherein the display panel is incorporated in the housing, wherein the rubber material is connected to the housing, and wherein the rubber material has a band-like shape.
-