

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12419131
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Guo; Zhiqiu et al.

Photovoltaic module and manufacturing method thereof

Abstract

A photovoltaic module, including a laminate including a solder strip; and a junction box arranged on a surface of the laminate and including a plate connected to the solder strip by laser soldering. The plate has a first region and a second region, in which a region covered by the solder strip on the plate is the first region, and a region not covered by the solder strip on the plate is the second region. A soldering seam formed by laser soldering includes a first soldering seam and a second soldering seam. The first soldering seam is located in the first region, and the first soldering seam extends through the solder strip into the plate along a thickness direction of the laminate. The second soldering seam is located in the second region, and the second soldering seam extends directly into the plate along the thickness direction of the laminate.

Inventors: Guo; Zhiqiu (Shanghai, CN), Hu; Yidong (Shanghai, CN), Yao; Yichao (Shanghai, CN)

Applicant: SHANGHAI JINKO GREEN ENERGY ENTERPRISE MANAGEMENT CO., LTD. (Shanghai, CN); ZHEJIANG JINKO SOLAR CO., LTD. (Zhejiang, CN)

Family ID: 1000008820294

Assignee: SHANGHAI JINKO GREEN ENERGY ENTERPRISE MANAGEMENT CO., LTD. (Shanghai, CN); ZHEJIANG JINKO SOLAR CO., LTD. (Zhejiang, CN)

Appl. No.: 18/529581

Filed: December 05, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240145618 A1	May. 02, 2024

Foreign Application Priority Data

CN	202211320245.3	Oct. 26, 2022
----	----------------	---------------

Related U.S. Application Data

continuation parent-doc US 18078676 20221209 US 11908971 child-doc US 18529581

Publication Classification

Int. Cl.: H10F71/00 (20250101); B23K1/005 (20060101); H10F19/00 (20250101); H10F77/00 (20250101)

U.S. Cl.:

CPC H10F71/00 (20250101); B23K1/0056 (20130101); H10F19/00 (20250101); H10F77/955 (20250101);

Field of Classification Search

CPC: H10F (71/00); H10F (77/955); H10F (19/00); B23K (1/0056)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
11908971	12/2023	Guo	N/A	H10F 71/00
2010/0247992	12/2009	Miyata et al.	N/A	N/A
2011/0285840	12/2010	Benson et al.	N/A	N/A
2012/0024373	12/2011	Dubbeldam	N/A	N/A
2013/0032207	12/2012	Oberriesser et al.	N/A	N/A
2019/0198691	12/2018	Fan et al.	N/A	N/A
2022/0224285	12/2021	Huang et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
102646741	12/2011	CN	N/A
104377263	12/2014	CN	N/A
104485884	12/2014	CN	N/A
208556647	12/2018	CN	N/A
210839471	12/2019	CN	N/A
212323016	12/2020	CN	N/A
114029572	12/2021	CN	N/A
114039260	12/2021	CN	N/A
114799525	12/2021	CN	N/A
102011052928	12/2011	DE	N/A
2517265	12/2016	EP	N/A
H08118012	12/1995	JP	N/A
2010153784	12/2009	JP	N/A
2015035436	12/2014	JP	N/A

OTHER PUBLICATIONS

Extended European Search Report issued in corresponding EP Application 22210452.3, issued Aug. 10, 2023, 8 pages. cited by applicant
Office Action issued in corresponding JP Application 2022-189426, issued Mar. 24, 2023, and an English Translation, 4 pages. cited by applicant
Examination Report issued in corresponding AU Application No. 2022279394, dated Dec. 18, 2023, 7 pages. cited by applicant
Notice of Allowance issued in corresponding JP Application No. 2023-144691, dated Jan. 30, 2024 with English Translation, 6 pages. cited by applicant
Examination Report issued in corresponding AU Application 2022279394, dated May 10, 2024, 5 pages. cited by applicant

Primary Examiner: Kang; Tae-Sik

Attorney, Agent or Firm: Burris Law, PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. application Ser. No. 18/078,676, filed on Dec. 9, 2022, which claims priority to Chinese Patent Application No. 202211320245.3, filed on Oct. 26, 2022. The disclosures of the above applications are incorporated herein by reference.

FIELD

(1) The present disclosure relates to the technical field of photovoltaic products, and in particular, to a photovoltaic module and a manufacturing method thereof.

BACKGROUND

(2) The statements in this section merely provide background information related to the present disclosure and may not constitute prior art.

(3) A junction box is a key connection device for a photovoltaic module to implement voltage output. In practice, an electrode of a laminate is required to be electrically connected to a plate in the junction box through a solder strip. In the related art, the solder strip is generally fixed and connected to the plate in the junction box by soldering, such as thermocompression bonding. On the one hand, a solder material needs to be prepared and molten in the soldering, which requires complicated machining operations. On the other hand, a melting point of the solder material is different from melting points of the solder strip and the plate, which is prone to desoldering due to thermal shock, resulting in poor reliability of the connection between the solder strip and the plate.

(4) The solder strip and the plate may also be fixed and connected by laser soldering. The plate and the solder strip can be directly molten to form a soldering seam by the laser soldering. Therefore, there is no need to provide any solder material and the connection is relatively reliable. However, the laser welding also has problems such as poor soldering efficiency.

SUMMARY

(5) This section provides a general summary of the disclosure and is not a comprehensive disclosure of its full scope or all of its features.

(6) The present disclosure provides a photovoltaic module and a manufacturing method thereof. The photovoltaic module improves production efficiency by reducing the difficulty of positioning prior to soldering.

(7) An embodiment of the present disclosure provides a photovoltaic module. The photovoltaic module includes: a laminate including a solder strip; and a junction box arranged on a surface of

the laminate and including a plate connected to the solder strip by laser soldering. The plate has a first region and a second region, in which a region covered by the solder strip on the plate is the first region, and a region not covered by the solder strip on the plate is the second region. A soldering seam formed by laser soldering includes a first soldering seam and a second soldering seam. The first soldering seam is located in the first region, and the first soldering seam extends through the solder strip into the plate along a thickness direction of the laminate. The second soldering seam is located in the second region, and the second soldering seam extends directly into the plate along the thickness direction of the laminate.

(8) In one or more embodiments, the soldering seam formed by laser soldering further comprises a third soldering seam having one part located in the first region and the other part located in the second region. Along the thickness direction of the laminate, the part of the third soldering seam located in the first region extends through the solder strip into the plate, and the part located in the second region extends directly into the plate.

(9) In one or more embodiments, the plate is provided with at least 6 soldering seams.

(10) In one or more embodiments, a sum of a number of the first soldering seam and a number of the third soldering seam is greater than or equal to three.

(11) In one or more embodiments, along the thickness direction of the laminate, a ratio of an extension depth of the part of the third soldering seam located in the first region within the plate to a thickness of the plate satisfies: $5\% \leq n1 \leq 60\%$; and/or a ratio of an extension depth of the part of the third soldering seam located in the second region within the plate to the thickness of the plate satisfies: $40\% \leq n2 \leq 80\%$.

(12) In one or more embodiments, along the thickness direction of the laminate, a ratio $n1$ of an extension depth of the first soldering seam within the plate to the thickness of the plate satisfies: $5\% \leq n1 \leq 60\%$; and/or a ratio $n2$ of an extension depth of the second soldering seam within the plate to the thickness of the plate satisfies: $40\% \leq n2 \leq 80\%$.

(13) In one or more embodiments, a width of the solder strip is $L1$, and a width of the plate is $L2$, and $L1$, $L2$ satisfy: $0.2 \leq L1/L2 \leq 0.8$.

(14) An embodiment of the present disclosure further provides a method for manufacturing a photovoltaic module, the photovoltaic module includes a laminate having a solder strip and a junction box having a plate. The method includes the following steps: providing the laminate; arranging the junction box on the laminate so that the solder strip of the laminate extends into the junction box; acquiring a position of the plate; pressing the solder strip against the plate in the junction box; laser-soldering the solder strip and the plate by using a laser head, a first soldering seam formed after soldering extends through the solder strip into the plate, and a second soldering seam extends directly into the plate; and visually inspecting the first soldering seam.

(15) In one or more embodiments, the step of acquiring a position of the plate includes: photographing the junction box; and acquiring the position of the plate according to a photographing result.

(16) In one or more embodiments, the plate has a first region and a second region, a region covered by the solder strip on the plate is the first region, and a region not covered by the solder strip on the plate is the second region; and in the step of laser-soldering the solder strip and the plate by using a laser head, the laser head emits lasers to the first region and the second region.

(17) In one or more embodiments, in the step of laser-soldering the solder strip and the plate by using a laser head, a power P of lasers emitted by the laser head satisfies: $550\text{ W} \leq P \leq 750\text{ W}$; and a soldering speed v of the laser head satisfies: $60\text{ mm/s} \leq v \leq 100\text{ mm/s}$.

(18) In one or more embodiments, the step of visually inspecting the first soldering seam includes: photographing the solder strip; and detecting whether a width d of a soldering seam on the solder strip satisfies: $0.3\text{ mm} \leq d \leq 0.4\text{ mm}$.

(19) It is to be understood that the general description above and the detailed description below are only examples and cannot limit the present disclosure.

(20) Further areas of applicability will become apparent from the description provided herein. It should be understood that the description and specific examples are intended for purposes of illustration only and are not intended to limit the scope of the present disclosure.

Description

DRAWINGS

- (1) In order that the disclosure may be well understood, there will now be described various forms thereof, given by way of example, reference being made to the accompanying drawings, in which:
- (2) FIG. 1 is a schematic structural diagram of a photovoltaic module according to one or more embodiments of the present disclosure;
- (3) FIG. 2 is a schematic structural diagram of the photovoltaic module according to one or more embodiments of the present disclosure;
- (4) FIG. 3 is a schematic structural diagram showing connection between a solder strip and a plate within a junction box in FIG. 1;
- (5) FIG. 4 is a schematic structural diagram of a first soldering seam and a second soldering seam in FIG. 3;
- (6) FIG. 5 is a schematic structural diagram of composition of the photovoltaic module according to one or more embodiments of the present disclosure;
- (7) FIG. 6 is a schematic structural diagram of a device for manufacturing a photovoltaic module according to one or more embodiments of the present disclosure; and
- (8) FIG. 7 is a flowchart of a method for manufacturing a photovoltaic module according to one or more embodiments of the present disclosure.
- (9) The accompanying drawings herein are incorporated in and constitute a part of this specification, illustrate embodiments consistent with the present disclosure and, together with the description, serve to explain the principles of the present disclosure.
- (10) The drawings described herein are for illustration purposes only and are not intended to limit the scope of the present disclosure in any way.

DETAILED DESCRIPTION

- (11) The following description is merely exemplary in nature and is not intended to limit the present disclosure, application, or uses. It should be understood that throughout the drawings, corresponding reference numerals indicate like or corresponding parts and features.
- (12) In order to better understand the technical solution of the present disclosure, embodiments of the present disclosure are described in detail below with reference to the accompanying drawings.
- (13) It is to be made clear that the described embodiments are only some rather than all of the embodiments of the present disclosure. All other embodiments obtained by those of ordinary skill in the art based on the embodiments in the present disclosure without creative efforts fall within the protection scope of the present disclosure.
- (14) The terms used in the embodiments of the present disclosure are intended only to describe particular embodiments and are not intended to limit the present disclosure. As used in the embodiments of the present disclosure and the appended claims, the singular forms of “a/an”, “the”, and “said” are intended to include plural forms, unless otherwise clearly specified by the context.
- (15) It is to be understood that the term “and/or” used herein is merely an association relationship describing associated objects, indicating that three relationships may exist. For example, A and/or B indicates that there are three cases of A alone, A and B together, and B alone. In addition, the character “/” herein generally means that associated objects before and after it are in an “or” relationship.
- (16) It is to be noted that the location terms such as “above”, “below”, “left”, and “right” described

in the embodiments of the present disclosure are described with reference to the angles shown in the accompanying drawings, and should not be construed as limitations on the embodiments of the present disclosure. In addition, in the context, it is to be further understood that, when one element is referred to as being connected “above” or “below” another element, the one element may be directly connected “above” or “below” another element, or connected “above” or “below” another element via an intermediate element.

(17) Embodiments of the present disclosure provide a photovoltaic module **10**. As shown in FIG. 1 and FIG. 3, the photovoltaic module **10** includes: a laminate **110** and a junction box **120**. The laminate **110** is provided with a solder strip **116**. The junction box **120** is arranged on a surface of the laminate **110**. The junction box **120** is provided with a plate **121**. The solder strip **116** is connected to the plate **121** by soldering, including arc soldering, argon arc soldering, carbon-dioxide arc soldering, laser soldering, electro-slag pressure soldering, and the like. Laser soldering is adopted in the present disclosure.

(18) The laminate **110** can generate a current under sunlight. The current generated is collected through the solder strip **116** and transported to the junction box **120**. The junction box **120** is first connected to other components in series through cables, and then electrically connected to an external electrical control device, so that the photovoltaic module **10** can supply power to the external electrical control device.

(19) As shown in FIG. 5, the laminate **110** is laminated by successively stacking a cover plate **111**, a first encapsulation adhesive film **112**, a group of solar cell strings **113**, a second encapsulation adhesive film **114**, and a back plate **115**. The group of solar cell strings **113** includes a plurality of solar cells **1131**. The solder strip **116** is electrically connected to the group of solar cell strings **113** and threaded through the back plate **115**, so as to derive electric energy of the solar cells **1131** in the group of solar cell strings **113**.

(20) The junction box **120** is generally arranged on a rear surface of the laminate **110**, that is, a position near the back plate **115**, which prevents the influence on photoelectric conversion efficiency of the laminate **110** due to the blocking by the junction box **120**. As shown in FIG. 2, the laminate **110** may be provided with one or more junction boxes **120**. For example, a number of the junction boxes **120** arranged on the laminate **110** may be 2 to 6, for example 3. The junction box **120** may be located at an edge of the laminate **110** or an inner side near the center of the laminate **110**. Further, the junction box **120**, when arranged at the inner side near the center of the laminate **110**, is arranged on, for example, a center line of the laminate **110**, and may further be arranged on a center line of a long side of the laminate **110**.

(21) The solder strip **116** is laser-soldered with the plate **121**. During the laser soldering, a high temperature is generated through energy of a laser beam to melt metal materials of the solder strip **116** and the plate **121**, so that the metal materials of the solder strip **116** and the plate **121** are fused and formed into an integrated structure after cooling and solidification. Thus, the connection between the solder strip **116** and the plate **121** is realized, and the connection is relatively reliable. In an embodiment, when the solder strip **116** and the plate **121** are made of a same material such as copper metal, fusion between the same metal of the solder strip **116** and the plate **121** can further improve strength of the connection between the solder strip **116** and the plate **121**, which is not prone to desoldering. In addition, during the laser soldering, since both the solder strip **116** and the plate **121** generate soldering seams through their own molten metal, there is no need to provide any further solder material, thereby facilitating the manufacturing process.

(22) As shown in FIG. 3, the plate **121** is provided with a first region and a second region. A region covered by the solder strip **116** on the plate **121** is the first region, and a region not covered by the solder strip **116** on the plate **121** is the second region. A soldering seam formed by laser soldering includes a first soldering seam **101** and a second soldering seam **102**. The first soldering seam **101** is located in the first region, and the first soldering seam **101** extends through the solder strip **116** into the plate **121** along a thickness direction of the laminate **110**. The second soldering seam **102** is

located in the second region, and the second soldering seam **102** extends directly into the plate **121** along the thickness direction of the laminate **110**. The second region may be on one side of the first region, or on both sides of the first region.

(23) In some embodiments, as shown in FIG. 3, soldering seams are formed in both the first region and the second region. That is, during the laser soldering of the solder strip **116** with the plate **121**, a soldering region includes the first region and the second region. Therefore, there is no need to accurately position the solder strip **116** prior to laser soldering, only the plate **121** is required to be positioned, and then the first region and the second region on the plate **121** are laser-soldered, which reduces difficulty of positioning prior to soldering and improves production efficiency, so as to achieve fast takt time of a production line.

(24) As shown in FIG. 3 and FIG. 4, when the first region and the second region on the plate **121** are laser-soldered, the first soldering seam **101** is formed in the first region, and the first soldering seam **101** extends through the solder strip **116** into the plate **121**, so as to realize a stable connection between the solder strip **116** and the plate **121**.

(25) In one or more embodiments, the soldering seam formed by laser soldering further includes a third soldering seam, the third soldering seam has one part located in the first region and the other part located in the second region. Along the thickness direction of the laminate **110**, the part of the third soldering seam located in the first region extends through the solder strip **116** into the plate **121**, and the part located in the second region extends directly into the plate **121**.

(26) The soldering seam extends generally along a length direction or a width direction of the plate **121**. During the laser soldering, both the first region and the second region on the plate **121** are laser-soldered. Therefore, an extension direction of the solder strip **116** above the plate **121** is not required to be parallel to an extension direction of the soldering seam, and part of the soldering seam can be formed on the solder strip **116**. That is, the extension direction of the solder strip **116** above the plate **121** may be inclined relative to the extension direction of the soldering seam, so as to reduce difficulty of flattening the solder strip **116** onto the plate **121** and further improving the production efficiency. In an embodiment, when the solder strip **116** is inclined relative to the length direction or the width direction of the plate **121** and the extension direction of the soldering seam is parallel to the width direction or the length direction of the plate **121**, the extension direction of the soldering seam is also inclined relative to the solder strip **116**. In this case, a third soldering seam may be formed by laser soldering. The third soldering seam has one part located in the first region and the other part located in the second region. That is, along a direction perpendicular to the thickness direction of the laminate **110**, the third soldering seam extends from the solder strip **116** to the plate **121** (or extends from the plate **121** to the solder strip **116**). In this way, it is more difficult for the solder strip **116** to be separated from the plate **121**, so that the connection between the solder strip **116** and the plate **121** is more reliable.

(27) It may be understood that, when the solder strip **116** is parallel to the length direction or the width direction of the plate **121** and the extension direction of the soldering seam is inclined relative to the width direction or the length direction of the plate **121**, the extension direction of the soldering seam is also inclined relative to the solder strip **116**. In this case, a third soldering seam may also be formed by laser soldering.

(28) In addition to a straight line shape, the soldering seam may also be in a curved shape or a wave shape. When the soldering seam is in a curved shape or a wave shape, an overall extension direction of the soldering seam may also be inclined relative to or parallel to the width direction or the length direction of the plate **121**. The following descriptions are all based on the soldering seam in the straight line shape.

(29) In some embodiments, as shown in FIG. 3, the plate **121** is provided with at least 6 soldering seams. For example, the number of the soldering seam may be 6, 7, 8, or the like.

(30) For example, as shown in FIG. 3, the number of the soldering seam on the plate **121** should not be excessively small. If the number of soldering seam is excessively small (for example, less

than 6), the number of the first soldering seam **101** falling into the first region will be correspondingly small, which brings poor reliability of the connection between the solder strip **116** and the plate **121**. Therefore, when the plate **121** is provided with at least 6 soldering seams by laser soldering, more first soldering seams **101** may fall into the first region, so as to ensure a relatively reliable connection between the solder strip **116** and the plate **121**.

(31) In some embodiments, a sum of numbers of the first soldering seam **101** and the third soldering seam is greater than or equal to three. For example, the sum of numbers of the first soldering seam **101** and the third soldering seam may be 3, 4, or the like.

(32) The sum of numbers of the first soldering seam **101** and the third soldering seam should not be excessively small. If the sum of numbers of the first soldering seam **101** and the third soldering seam is excessively small (for example, less than 3), the reliability of the connection between the solder strip **116** and the plate **121** is low. Therefore, a relatively reliable connection between the solder strip **116** and the plate **121** can be ensured when the sum of numbers of the first soldering seam **101** and the third soldering seam is greater than or equal to three.

(33) In some embodiments, as shown in FIG. 4, along the thickness direction of the laminate **110**, a ratio $n1$ of an extension depth of the first soldering seam **101** within the plate **121** to a thickness of the plate **121** satisfies: $5\% \leq n1 \leq 60\%$; and/or a ratio $n2$ of an extension depth of the second soldering seam **102** within the plate **121** to the thickness of the plate **121** satisfies: $40\% \leq n2 \leq 80\%$. For example, the ratio $n1$ may be 5%, 10%, 20%, 40%, 60%, or the like, and the ratio $n2$ may be 40%, 50%, 60%, 70%, 80%, or the like.

(34) It is to be noted that the extension depth of the soldering seam within the plate **121** is related to irradiation power and irradiation duration of lasers. Since irradiation power and irradiation duration of lasers during the laser welding are generally fixed, the extension depth of the second soldering seam **102** within the plate **121** is greater than the extension depth of the first soldering seam **101** within the plate **121**, and the extension depth of the second soldering seam **102** within the plate **121** increases as the extension depth of the first soldering seam **101** within the plate **121** increases.

(35) As shown in FIG. 4, along the thickness direction of the laminate **110**, the ratio $n1$ of the extension depth of the first soldering seam **101** within the plate **121** to the thickness of the plate **121** should not be excessively small or excessively large; and/or the ratio $n2$ of the extension depth of the second soldering seam **102** within the plate **121** to the thickness of the plate **121** should not be excessively small or excessively large. If the ratio $n1$ is excessively small (for example, less than 5%), the extension depth of the first soldering seam **101** within the plate **121** is excessively small, poor contact easily occurs between the solder strip **116** and the plate **121**, which adversely affects power supply of the photovoltaic module **10** to the external electrical control device. If the ratio $n1$ is excessively large (for example, greater than 60%), the ratio $n2$ is also excessively large (for example, greater than 80%), as a result, the second soldering seam **102** may penetrate through the plate **121** and touch the bottom of the junction box **120**, thereby damaging the laminate **110**.

(36) Therefore, along the thickness direction of the laminate **110**, when the ratio $n1$ of the extension depth of the first soldering seam **101** within the plate **121** to the thickness of the plate **121** satisfies: $5\% \leq n1 \leq 60\%$, and/or the ratio $n2$ of the extension depth of the second soldering seam **102** within the plate **121** to the thickness of the plate **121** satisfies: $40\% \leq n2 \leq 80\%$, damages to the laminate **110** caused by penetration of the second soldering seam **102** through the plate **121** can be effectively prevented and the reliability of the connection between the solder strip **116** and the plate **121** is thus ensured.

(37) In some embodiments, along the thickness direction of the laminate **110**, a ratio of an extension depth of the part of the third soldering seam located in the first region within the plate **121** to a thickness of the plate **121** satisfies: $5\% \leq n1 \leq 60\%$; and/or a ratio of an extension depth of the part of the third soldering seam located in the second region within the plate **121** to the thickness of the plate **121** satisfies: $40\% \leq n2 \leq 80\%$.

(38) Since the part of the third soldering seam located in the first region extends through the solder

strip **116** into the plate **121**, extension of the part of the third soldering seam located in the first region within the plate **121** is similar to the extension of the first soldering seam **101** within the plate **121**. Since the part of the third soldering seam located in the second region extends directly into the plate **121**, extension of the part of the third soldering seam located in the second region within the plate **121** is similar to the extension of the second soldering seam **102** within the plate **121**.

(39) In addition, due to possible error in the manufacturing device or possible error in the method for manufacturing the photovoltaic module **10**, extension depths of adjacent first soldering seams **101** in the first region within the plate **121** may differ greatly or extension depths of adjacent second soldering seams **102** in the second region within the plate **121** may differ greatly. In actual production, a ratio of a difference between the extension depths of the adjacent first soldering seams **101** or second soldering seams **102** within the plate **121** to the thickness of the plate **121** may be up to 20%. Therefore, in the present disclosure, a larger range is set for the extension depths of the first soldering seam **101**, the second soldering seam **102**, and the third soldering seam within the plate **121**, which reduces requirements on accuracy of the manufacturing device and the method for manufacturing the photovoltaic module **10**.

(40) In some embodiments, as shown in FIG. 3, a width of the solder strip **116** is L_1 , and a width of the plate **121** is L_2 , which satisfy: $0.2 \leq L_1/L_2 \leq 0.8$. For example, L_1/L_2 may be, 0.2, 0.4, 0.6, 0.8, or the like.

(41) As shown in FIG. 3, the width L_1 of the solder strip **116** is also a width of the first region, and the width L_2 of the plate **121** is also widths of the first region and the second region. The ratio L_1/L_2 of the width L_1 of the solder strip **116** to the width L_2 of the plate **121** should not be excessively large or excessively small. If the ratio L_1/L_2 is excessively large (for example, greater than 0.8), the width of the plate **121** is excessively small, which increases the difficulty of positioning the plate **121** prior to soldering and the time required by the positioning, and thus reduces manufacturing efficiency of the photovoltaic module **10**. If the ratio L_1/L_2 is excessively small (for example, less than 0.2), the width of the plate **121** is excessively large, and only a small number of soldering seams or no soldering seam may extend through the solder strip **116** to the plate **121**, resulting in an unreliable connection or no connection between the solder strip **116** and the plate **121**. Therefore, the reliability of the connection and the manufacturing efficiency of the solder strip **116** and the plate **121** can be ensured only when the ratio L_1/L_2 of the width L_1 of the solder strip **116** to the width L_2 of the plate **121** satisfies: $0.2 \leq L_1/L_2 \leq 0.8$.

(42) As shown in FIG. 5, a device for manufacturing a photovoltaic module **10** includes: a carrying mechanism **20**, a pressing mechanism **30**, a laser head **40**, a first detector **50**, and a second detector **60**. The carrying mechanism **20** is configured to carry the photovoltaic module **10** and drive the photovoltaic module **10** to move. The pressing mechanism **30** is configured to press the solder strip **116** against the plate **121**. The laser head **40** is configured to laser-solder the solder strip **116** with the plate **121**. The first detector **50** is configured to position the plate **121**. The second detector **60** is configured to detect soldering seams.

(43) The present disclosure further provides a method for manufacturing a photovoltaic module. As shown in FIG. 6 and FIG. 7, the method for manufacturing a photovoltaic module includes the following steps:

(44) In S1, the laminate **110** is provided.

(45) In this step, the laminate **110** is placed on the carrying mechanism **20**.

(46) In S2, the junction box **120** is arranged on the laminate **110** so that the solder strip **116** of the laminate **110** extends into the junction box **120**.

(47) In this step, the junction box **120** is provided with an opening that enables the solder strip **116** to pass through. The junction box **120** is placed corresponding to the solder strip **116** so that the solder strip **116** passes through the opening.

(48) In S3, a position of the plate **121** is acquired.

(49) In this step, the first detector **50** can detect the position of the plate **121**. The first detector **50** may be a CCD visual inspection system or the like.

(50) In **S4**, the solder strip **116** is pressed against the plate **121** in the junction box **120**.

(51) In this step, the pressing mechanism **30** can move relative to the carrying mechanism **20**, so as to contact the solder strip **116** to press the solder strip **116** against the plate **121**.

(52) In some embodiments, the junction box **120** is further provided with a diode **122**. The diode **122** can be electrically connected to the solder strip **116** and configured to protect the photovoltaic module **10** from anomaly. The plate **121** in the junction box **120** may be formed by a conductive terminal part of the diode **122**. That is, the conductive terminal part of the diode **122** is extended into a plane shape with a certain area, in order to realize a connection with the solder strip **116**. The plate **121** in the junction box **120** may also be an individual plate component. That is, the individual plate component is secured to the junction box **120** through a fastener such as an anchor, and the individual plate component is connected to the conductive terminal of the diode **122**.

(53) In **S5**, the solder strip **116** is laser-soldered with the plate **121** by using a laser head **40**, a first soldering seam **101** formed after soldering extends through the solder strip **116** into the plate **121**, and a second soldering seam **102** extends directly into the plate **121**.

(54) In this step, the laser head **40** may emit a laser of specific power to realize the soldering of the solder strip **116** with the plate **121**.

(55) When the laser emitted by the laser head **40** irradiates the first region, the laser may melt the solder strip **116** and the plate **121**, and as the laser head **40** moves, the first soldering seam **101** may be formed on the path of the laser. When the laser emitted by the laser head **40** irradiates the second region, the laser may melt the plate **121**, and as the laser head **40** moves, the second soldering seam **102** may be formed on the path of the laser. When the path of the laser emitted by the laser head **40** spans the first region and the second region, a third soldering seam may be formed on the path of the laser.

(56) In **S6**, the first soldering seam **101** is visually inspected.

(57) In this step, it may be determined whether the soldering seam formed after soldering satisfies the requirement by visual inspection on the soldering seam after laser soldering, so as to ensure the production yield of the photovoltaic module **10**.

(58) In some embodiments, in step **S3**, the step of acquiring a position of the plate **121** includes the following steps:

(59) In **S31**, the junction box **120** is photographed.

(60) In **S32**, the position of the plate **121** is acquired according to the photographing result.

(61) The first detector **50** can photograph the junction box **120** so as to acquire the position of the plate **121** according to a shot image, so that the solder strip **116** is soldered onto the plate **121**.

(62) For example, in the step **S5** of laser-soldering the solder strip **116** with the plate **121** by using a laser head **40**, the laser head **40** emits lasers to the first region and the second region.

(63) In some embodiments, as shown in FIG. 6 and FIG. 7, the laser soldering on both the first region and the second region reduces the difficulty of positioning the solder strip **116** and improves manufacturing efficiency of the photovoltaic module **10**, so as to achieve fast takt time of the production line.

(64) In the step **S5** of laser-soldering the solder strip **116** with the plate **121** by using a laser head **40**, power P of lasers emitted by the laser head **40** satisfies: $550\text{ W} \leq P \leq 750\text{ W}$; and a soldering speed v of the laser head **40** satisfies: $60\text{ mm/s} \leq v \leq 100\text{ mm/s}$. For example, the power P may be 550 W, 600 W, 650 W, 700 W, 750 W, or the like, and the soldering speed v may be, 60 mm/s, 70 mm/s, 80 mm/s, 90 mm/s, 100 mm/s, or the like.

(65) In this embodiment, through the control over the soldering power P of the laser head **40**, intensity of energy of the laser emitted by the laser head **40** when reaching a surface of the solder strip **116** can be controlled, so as to control the intensity of the energy of the laser reaching the surface of the solder strip **116** during the soldering to be within a reasonable range. An

insufficiently reliable connection between the solder strip **116** and the plate **121** due to a shallow soldering depth caused by low intensity of the energy of the laser (for example, when the soldering power P is less than 550 W) is prevented, and the problem of melt-through of the plate **121** caused by relatively high energy of the laser (for example, when the soldering power P is greater than 750 W) is also prevented.

(66) In addition, through the control over the soldering speed v of the laser head **40**, the width of the soldering seam can be controlled, so that the soldering seam finally formed meets quality requirements. An excessively wide soldering seam due to long stay time of the laser in a soldering region caused by an excessively low soldering speed v (for example, when the soldering speed v is less than 60 mm/s) is prevented, and an excessively narrow soldering seam due to an excessively high soldering speed v (for example, when the soldering speed v is greater than 100 mm/s) is also prevented.

(67) In some embodiments, step **S6** of visually inspecting the first soldering seam **101** includes the following steps:

(68) In **S61**, the solder strip **116** is photographed.

(69) In **S62**, it is detected whether a width d of a soldering seam on the solder strip **116** satisfies: $0.3\text{ mm} \leq d \leq 0.4\text{ mm}$. For example, the width d of the soldering seam may be 0.3 mm, 0.32 mm, 0.35 mm, 0.38 mm, 0.4 mm, or the like.

(70) The carrying mechanism **20** can move the photovoltaic module **10** after the soldering below the second detector, and the second detector **60** can photograph the solder strip **116** on the plate **121** and detect the width of the soldering seam on the solder strip **116**. Since the width d of the soldering seam can reflect quality of soldering to some extent, it may be determined, through the width d of the soldering seam on the surface of the solder strip **116**, whether the quality of soldering meets the requirement, so as to ensure the production yield of the photovoltaic module **10**.

(71) If the width d of the first soldering seam **101** is excessively small (for example, less than 0.3 mm) or the width d of the first soldering seam **101** is excessively large (for example, greater than 0.4 mm), it is considered that the quality of soldering does not meet the requirement. It is considered that the quality of soldering meets the requirement only when the width d of the first soldering seam **101** satisfies: $0.3\text{ mm} \leq d \leq 0.4\text{ mm}$.

(72) The above are merely some embodiments of the present disclosure, and are not intended to limit the present disclosure. For those skilled in the art, the present disclosure may be subject to various modifications and changes. Any modification, equivalent replacement, improvement and the like within the spirit and principle of the present disclosure all fall within the protection scope of the present disclosure.

(73) Unless otherwise expressly indicated herein, all numerical values indicating mechanical/thermal properties, compositional percentages, dimensions and/or tolerances, or other characteristics are to be understood as modified by the word “about” or “approximately” in describing the scope of the present disclosure. This modification is desired for various reasons including industrial practice, material, manufacturing, and assembly tolerances, and testing capability.

(74) As used herein, the phrase at least one of A, B, and C should be construed to mean a logical (A OR B OR C), using a non-exclusive logical OR, and should not be construed to mean “at least one of A, at least one of B, and at least one of C.”

(75) The description of the disclosure is merely exemplary in nature and, thus, variations that do not depart from the substance of the disclosure are intended to be within the scope of the disclosure. Such variations are not to be regarded as a departure from the spirit and scope of the disclosure.

Claims

1. A photovoltaic module, comprising: a laminate including a solder strip; and a junction box arranged on a surface of the laminate and including a plate connected to the solder strip by soldering; wherein the plate includes a first region covered by the solder strip and a second region not covered by the solder strip; and wherein a first soldering seam formed by soldering is located in the first region and extends, along a thickness direction of the laminate, through the solder strip into the plate, and a second soldering seam formed by soldering is located in the second region and extends, along the thickness direction of the laminate, directly into the plate.
2. The photovoltaic module according to claim 1, wherein a third soldering seam formed by soldering includes one part located in the first region and the other part located in the second region; and along the thickness direction of the laminate, the one part of the third soldering seam located in the first region extends through the solder strip into the plate, and the other part located in the second region extends directly into the plate.
3. The photovoltaic module according to claim 2, wherein the plate is provided with at least 6 soldering seams.
4. The photovoltaic module according to claim 2, wherein a sum of a number of the first soldering seam and a number of the third soldering seam is greater than or equal to three.
5. The photovoltaic module according to claim 2, wherein, along the thickness direction of the laminate, a ratio n_1 of an extension depth of the one part of the third soldering seam located in the first region within the plate to a thickness of the plate satisfies: $5\% \leq n_1 \leq 60\%$.
6. The photovoltaic module according to claim 2, wherein, along the thickness direction of the laminate, a ratio n_2 of an extension depth of the other part of the third soldering seam located in the second region within the plate to a thickness of the plate satisfies: $40\% \leq n_2 \leq 80\%$.
7. The photovoltaic module according to claim 2, wherein the first soldering seam, the second soldering seam and/or the third soldering seam has a straight line shape, a curved shape or a wave shape.
8. The photovoltaic module according to claim 2, wherein the first soldering seam, the second soldering seam and/or the third soldering seam is inclined relative to the solder strip or the plate.
9. The photovoltaic module according to claim 1, wherein, along the thickness direction of the laminate, a ratio of an extension depth of the first soldering seam within the plate to the thickness of the plate is in a range of 5% to 60%.
10. The photovoltaic module according to claim 1, wherein, along the thickness direction of the laminate, a ratio of an extension depth of the second soldering seam within the plate to the thickness of the plate is in a range of 40% to 80%.
11. The photovoltaic module according to claim 1, wherein a width of the solder strip is L_1 , a width of the plate is L_2 , and L_1, L_2 satisfy: $0.2 \leq L_1/L_2 \leq 0.8$.
12. The photovoltaic module according to claim 1, wherein the junction box is arranged on a central line of a long side of the laminate.
13. The photovoltaic module according to claim 1, wherein the solder strip and the plate are made of the same material.
14. A method for manufacturing the photovoltaic module according to claim 1, comprising: providing the laminate; arranging the junction box on the laminate so that the solder strip of the laminate extends into the junction box; pressing the solder strip against the plate in the junction box; and laser-soldering the solder strip and the plate by using a laser head, so that the first soldering seam formed after the laser-soldering extends through the solder strip into the plate, and the second soldering seam extends directly into the plate.
15. The method according to claim 14, wherein prior to the pressing the solder strip against the plate in the junction box, the method further comprises: acquiring a position of the plate.

16. The method according to claim 15, wherein the acquiring a position of the plate comprises: photographing the junction box; and acquiring the position of the plate according to a photographing result.

17. The method according to claim 14, wherein subsequent to the laser-soldering the solder strip and the plate by using a laser head, the method further comprises: visually inspecting the first soldering seam.

18. The method according to claim 14, wherein during the laser-soldering the solder strip and the plate by using a laser head, the laser head emits lasers to the first region and the second region.

19. The method according to claim 14, wherein, during the laser-soldering the solder strip and the plate by using a laser head, a power P of lasers emitted by the laser head satisfies: $550\text{ W} \leq P \leq 750\text{ W}$; and a soldering speed v of the laser head satisfies: $60\text{ mm/s} \leq v \leq 100\text{ mm/s}$.

20. The method according to claim 17, wherein the visually inspecting the first soldering seam comprises: photographing the solder strip; and detecting whether a width d of a soldering seam on the solder strip satisfies:

$0.3\text{ mm} \leq d \leq 0.4\text{ mm}$.
