

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285951

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

KIM; Dahee et al.

SEMICONDUCTOR PACKAGE INCLUDING REDISTRIBUTION PATTERN

Abstract

A semiconductor package includes a semiconductor chip including a connecting pad, a mold layer covering the semiconductor chip, a lower redistribution layer on the semiconductor chip and the mold layer, and a connecting terminal on the lower redistribution layer. The lower redistribution layer includes a first lower insulating layer, a first conformal redistribution pattern extending through the first lower insulating layer, a second lower insulating layer on the first lower insulating layer and the first conformal redistribution pattern, and a first filled redistribution pattern disposed on the first conformal redistribution pattern and extending through the second lower insulating layer. A side surface of the first filled redistribution pattern is spaced apart from an inner side surface of the first conformal redistribution pattern. The second lower insulating layer is between the inner side surface of the first conformal redistribution pattern and the side surface of the first filled redistribution pattern.

Inventors: KIM; Dahee (Cheonan-si, KR), SONG; Gookmi (Hwaseong-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 1000008619474

Assignee: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Appl. No.: 19/214815

Filed: May 21, 2025

Foreign Application Priority Data

KR 10-2021-0078640

Jun. 17, 2021

Related U.S. Application Data

parent US continuation 17695110 20220315 PENDING child US 19214815

Publication Classification

Int. Cl.: **H01L23/498** (20060101); **H01L23/00** (20060101); **H01L23/31** (20060101); **H01L25/10** (20060101)

U.S. Cl.:

CPC **H01L23/49822** (20130101); **H01L23/3128** (20130101); **H01L24/08** (20130101); **H01L25/105** (20130101); H01L2224/08235 (20130101); H01L2225/1058 (20130101)

Background/Summary

CROSS-REFERENCE TO THE RELATED APPLICATION [0001] This is a continuation of U.S. application Ser. No. 17/695,110, filed Mar. 15, 2022, which claims priority to Korean Patent Application No. 10-2021-0078640, filed on Jun. 17, 2021, in the Korean Intellectual Property Office, the disclosures of each of which are incorporated herein by reference in its entirety.

BACKGROUND

1. Field

[0002] The example embodiments of the disclosure relate to semiconductor packages including a redistribution pattern.

2. Description of the Related Art

[0003] In accordance with advances in electronics industries, development of a variety of technologies for achieving an enhancement in reliability and miniaturization of a semiconductor package is required. In order to meet such a requirement of an enhancement in reliability and miniaturization of a semiconductor package, active research on technology using a redistribution line is being conducted.

SUMMARY

[0004] The example embodiments of the disclosure provide semiconductor packages capable of eliminating a problem caused by a coefficient of thermal expansion difference between a semiconductor chip and a redistribution pattern in a semiconductor package using a redistribution line.

[0005] A semiconductor package according to an example embodiment of the disclosure may include a semiconductor chip including a connecting pad, a mold layer covering the semiconductor chip, a lower redistribution layer on the semiconductor chip and the mold layer, and a connecting terminal on the lower redistribution layer. The lower redistribution layer may include a first lower insulating layer, a first conformal redistribution pattern extending through the first lower insulating layer, a second lower insulating layer on the first lower insulating layer and the first conformal redistribution pattern, and a first filled redistribution pattern on the first conformal redistribution pattern, the first filled redistribution pattern extending through the second lower insulating layer. A side surface of the first filled redistribution pattern may be spaced apart from an inner side surface of the first conformal redistribution pattern. The second lower insulating layer may be between the inner side surface of the first conformal redistribution pattern and the side surface of the first filled redistribution pattern.

[0006] A semiconductor package according to an example embodiment of the disclosure may include a base layer including an opening, a conductive connector extending through the base layer, a semiconductor chip in the opening, a mold layer covering a top surface of each of the base layer and the semiconductor chip, and a lower redistribution layer on the base layer, the semiconductor chip and the mold layer. The semiconductor chip may include a die, a chip pad on the die, and a

connecting pad on the chip pad. The connecting pad may include a first top surface, a second top surface, and an inner side surface interconnecting the first top surface and the second top surface. The lower redistribution layer may include a first lower insulating layer on the semiconductor chip, a first lower redistribution pattern extending through the first lower insulating layer, the first lower redistribution pattern including a first via contacting the first top surface of the connecting pad, and a first conductive pad on the first via, and a second lower redistribution pattern on the first lower redistribution pattern. A side surface of the first via may be spaced apart from the inner side surface of the connecting pad. The first lower insulating layer may be between the side surface of the first via and the inner side surface of the connecting pad.

[0007] A semiconductor package according to an example embodiment of the disclosure may include a semiconductor chip including a chip pad, a mold layer covering the semiconductor chip, a lower redistribution layer on a bottom surface of the mold layer, and a conductive connector connected to the lower redistribution layer and extending through the mold layer. The lower redistribution layer may include an under bump metal (UBM), a first lower insulating layer covering the UBM, a first conformal redistribution pattern on the UBM, the first conformal redistribution pattern extending through the first lower insulating layer, a second lower insulating layer on the first conformal redistribution pattern, and a first filled redistribution pattern on the first conformal redistribution pattern, the first filled redistribution pattern extending through the second lower insulating layer. A side surface of the first filled redistribution pattern may be spaced apart from an inner side surface of the first conformal redistribution pattern. The second lower insulating layer may be between the inner side surface of the first conformal redistribution pattern and the side surface of the first filled redistribution pattern.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] FIG. 1 is a sectional view of a semiconductor package according to an example embodiment of the disclosure.

[0009] FIG. 2 is an enlarged view of a portion A of FIG. 1.

[0010] FIG. 3 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0011] FIG. 4 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0012] FIG. 5 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0013] FIG. 6 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0014] FIG. 7 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0015] FIG. 8 is a sectional view of a semiconductor package according to an example embodiment of the disclosure.

[0016] FIG. 9 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0017] FIG. 10 is a sectional view of a semiconductor package according to an example embodiment of the disclosure.

[0018] FIG. 11 is an enlarged view of a portion of a semiconductor package according to an example embodiment of the disclosure.

DETAILED DESCRIPTION

[0019] When the terms “about” or “substantially” are used in this specification in connection with a

numerical value, it is intended that the associated numerical value includes a manufacturing or operational tolerance (e.g., $\pm 10\%$) around the stated numerical value. Moreover, when the words “about” and “substantially” are used in connection with geometric shapes, it is intended that precision of the geometric shape is not required but that latitude for the shape is within the scope of the disclosure. Further, regardless of whether numerical values or shapes are modified as “about” or “substantially,” it will be understood that these values and shapes should be construed as including a manufacturing or operational tolerance (e.g., $\pm 10\%$) around the stated numerical values or shapes.

[0020] FIG. 1 is a sectional view of a semiconductor package according to an example embodiment of the disclosure.

[0021] Referring to FIG. 1, a semiconductor package **100** may include a lower semiconductor package **100A**, and an upper semiconductor package **100B** on the lower semiconductor package **100A**. The upper semiconductor package **100B** may be disposed on the lower semiconductor package **100A** via connecting terminals **190**.

[0022] The lower semiconductor package **100A** may include a base layer **110**, a conductive connector **120**, a semiconductor chip **130**, a mold layer **140**, a lower redistribution layer **150**, connecting terminals **160**, and an upper redistribution layer **171/CP_U**.

[0023] The base layer **110** may be disposed outside the semiconductor chip **130**. The base layer **110** may have, at a central portion thereof, an opening OP extending through the base layer **110** in a first direction D1, and may be a plate having a quadrangular rim shape when viewed in a top view. The semiconductor chip **130** may be disposed in the opening OP. When viewed in a top view, the base layer **110** may surround a side surface of the semiconductor chip **130**. The size of the opening OP may be greater than the size of the semiconductor chip **130**. The semiconductor chip **130** and the base layer **110** may be spaced apart from each other in a second direction D2. The second direction D2 may perpendicularly intersect the first direction D1.

[0024] The base layer **110** may have a multilayer structure. For example, the base layer **110** may include a first base layer **111** and a second base layer **113**. The first base layer **111** and the second base layer **113** may be sequentially stacked on a top surface of the lower redistribution layer **150** in a direction opposite to the first direction D1. The first base layer **111** may be disposed on the lower redistribution layer **150**, and the second base layer **113** may be disposed on the first base layer **111**. For example, the base layer **110** may include at least one of phenol resin, epoxy resin, and polyimide. For example, the base layer **110** may include at least one of flame retardant 4 (FR4), tetrafunctional epoxy, polyphenylene ether, bismaleimide triazine (BT), epoxy/polyphenylene oxide, Thermount, cyanate ester, polyimide, and liquid crystal polymer.

[0025] At least some of the conductive connector **120** may extend through the base layer **110**, and thus may electrically interconnect the lower redistribution layer **150** and the upper redistribution layer **171/CP_U**. The conductive connector **120** may include conductive vias **121a** and **121b**, and conductive pads **123a**, **123b** and **123c**. The conductive vias **121a** and **121b** may include a first conductive via **121a** and a second conductive via **121b**. The conductive pads **123a**, **123b** and **123c** may include a first conductive pad **123a**, a second conductive pad **123b**, and a third conductive pad **123c**. The first conductive pad **123a** may be disposed on a bottom surface of the first base layer **111**, the second conductive pad **123b** may be disposed on a top surface of the first base layer **111**, and the first conductive via **121a** may extend through the first base layer **111**, and thus may interconnect the first conductive pad **123a** and the second conductive pad **123b**. The third conductive pad **123c** may be disposed on a top surface of the second base layer **113**, the second conductive via **121b** may extend through the second base layer **113**, and thus may interconnect the second conductive pad **123b** and the third conductive pad **123c**.

[0026] The semiconductor chip **130** may be disposed in the opening OP of the base layer **110**. The semiconductor chip **130** may include a die **131**, chip pads **133**, a first passivation layer **135**, a second passivation layer **137**, and connecting pads **139**. The die **131** may include at least one of

silicon, germanium, and gallium arsenide. Various circuits may be formed at the die **131**. The chip pads **133** may be disposed on a bottom surface **10B** of the die **131**. The chip pads **133** may include a conductive material. The first passivation layer **135** may cover a portion of the bottom surface **10B** of the die **131**, a portion of a bottom surface of each chip pad **133** and a side surface of each chip pad **133**. The first passivation layer **135** may expose a portion of the bottom surface of each chip pad **133**. For example, the first passivation layer **135** may include silicon oxide and/or silicon nitride. The second passivation layer **137** may cover the first passivation layer **135**. The first passivation layer **135** may be disposed between the second passivation layer **137** and the die **131** and between the second passivation layer **137** and the chip pads **133**. The second passivation layer **137** may expose the chip pads **133** through the first passivation layer **135** exposing the chip pads **133**. A plurality of openings **OP1** (cf. FIG. 2) respectively exposing the chip pads **133** may be formed at the first passivation layer **135** and the second passivation layer **137**. For example, the second passivation layer **137** may include photosensitive polyimide (PSPI). The connecting pads **139** may be connected to the chip pads **133**, respectively. The connecting pads **139** may be connected to the chip pads **133** through the openings **OP1** (cf. FIG. 2) of the first passivation layer **135** and the second passivation layer **137**, respectively. The connecting pads **139** may contact the first passivation layer **135** through the openings **OP1** (cf. FIG. 2). The connecting pads **139** may cover a portion of a bottom surface of the second passivation layer **137**. The connecting pads **139** may include a conductive material.

[0027] The mold layer **140** may be disposed on the semiconductor chip **130** and the base layer **110**. The mold layer **140** may fill the opening **OP** of the base layer **110** while extending between the semiconductor chip **130** and the base layer **110**. The mold layer **140** may cover a side surface and a top surface **10U** of the semiconductor chip **130**, and may cover a top surface and an inner side surface of the base layer **110**. For example, the mold layer **140** may include an epoxy molding compound (EMC).

[0028] The lower redistribution layer **150** may be disposed on the base layer **110**, the semiconductor chip **130** and the mold layer **140**. The lower redistribution layer **150** may be disposed on the bottom surface **10B** of the die **131** of the semiconductor chip **130**. The lower redistribution layer **150** may include lower insulating layers **151**, lower redistribution patterns **CP**, and under bump metals (UBMs) **159**. The lower insulating layers **151** may include a first lower insulating layer **151a**, a second lower insulating layer **151b**, a third lower insulating layer **151c**, and a fourth lower insulating layer **151d**. The first to fourth lower insulating layers **151a**, **151b**, **151c** and **151d** may be sequentially stacked on a bottom surface of the base layer **110** and a bottom surface of the semiconductor chip **130** in the first direction **D1**. For example, the first to fourth lower insulating layers **151a**, **151b**, **151c** and **151d** may include a curable material. That is, the lower insulating layers **151** may be a material cured by heat or light. For example, the curable material included in the first to fourth lower insulating layers **151a**, **151b**, **151c** and **151d** may include an inorganic material such as silicon oxide, silicon nitride or a silicon oxynitride and/or a polyamide series polymer material. For example, the curable material included in the lower insulating layers **151** may include at least one of photosensitive polyimide (PSPI), polybenzoxazole (PBO), a phenolic polymer, a benzocyclobutene (BCB) series polymer and an epoxy series polymer.

[0029] The lower redistribution patterns **CP** may be disposed in the lower insulating layers **151**. The lower redistribution patterns **CP** may include a first lower redistribution pattern **153**, a second lower redistribution pattern **155**, and a third lower redistribution pattern **157**. The first to third lower redistribution patterns **153**, **155** and **157** may be sequentially stacked in the first direction **D1**. The first lower redistribution pattern **153** may be directly connected to the connecting pad **139**. A portion of the first lower redistribution pattern **153** may extend through the first lower insulating layer **151a**, and another portion of the lower redistribution pattern **153** may be disposed on a bottom surface of the first lower insulating layer **151a**. The second lower redistribution pattern **155**

may be connected to the first lower redistribution pattern **153**. A portion of the second lower redistribution pattern **155** may extend through the second lower insulating layer **151b**, and another portion of the second lower redistribution pattern **155** may be disposed on a bottom surface of the second lower insulating layer **151b**. The third lower redistribution pattern **157** may be connected to the second lower redistribution pattern **155**. A portion of the third lower redistribution pattern **157** may extend through the third lower insulating layer **151c**, and another portion of the third lower redistribution pattern **157** may be disposed on a bottom surface of the third lower insulating layer **151c**. The lower redistribution patterns CP may include a conductive material. For example, the lower redistribution patterns CP may include copper.

[0030] The UBMs **159** may be electrically connected to the lower redistribution patterns CP. The UBMs **159** may be directly connected to the third lower redistribution pattern **157**. A portion of each UBM **159** may be connected to a bottom surface of the third lower redistribution pattern **157** while extending through the fourth lower insulating layer **151d**, and another portion of each UBM **159** may be disposed on a bottom surface of the fourth lower insulating layer **151d**. The UBMs **159** may include a conductive material.

[0031] The connecting terminals **160** may be disposed on a bottom surface of the lower redistribution layer **150**. The connecting terminals **160** may be connected to the UBMs **159**, respectively. The connecting terminals **160** may be disposed on bottom surfaces of the UBMs **159**, respectively. The connecting terminals **160** may be electrically connected to the semiconductor chip **130** and/or the conductive connector **120** via the UBMs **159** and the lower redistribution patterns CP.

[0032] The upper redistribution layer **171/CP_U** may be disposed on the mold layer **140**. The upper redistribution layer **171/CP_U** may be disposed on the top surface **10U** of the semiconductor chip **130**. The upper redistribution layer **171/CP_U** may include upper insulating layers **171** and upper redistribution patterns CP_U. The upper insulating layers **171** may include a first upper insulating layer **171a**, a second upper insulating layer **171b**, and a third upper insulating layer **171c**. The first to third upper insulating layers **171a**, **171b** and **171c** may be sequentially stacked on the mold layer **140** in the direction opposite to the first direction **D1**. The upper insulating layers **171** may include the same material as the lower insulating layers **151**.

[0033] The upper redistribution patterns CP_U may be disposed in the upper insulating layers **171**. The upper redistribution patterns CP_U may include a first upper redistribution pattern **173**, a second upper redistribution pattern **175**, a third upper redistribution pattern **177**, and an upper pad **179**. The first upper redistribution pattern **173** may be connected to the third conductive pad **123c** while extending through the mold layer **140**. The first upper insulating layer **171a** may cover a portion of the first upper redistribution pattern **173**. The second upper redistribution pattern **175** may be connected to the first upper redistribution pattern **173** while extending through the first upper insulating layer **171a**. The second upper insulating layer **171b** may cover a portion of the second upper redistribution pattern **175**. The third upper redistribution pattern **177** may be disposed on the second upper redistribution pattern **175**. The upper pad **179** may be disposed on the third upper redistribution pattern **177**. The third upper insulating layer **171c** may cover a portion of the third upper redistribution pattern **177** and a portion of the upper pad **179**. The third upper insulating layer **171c** may expose a top surface of the upper pad **179**. The connecting terminal **190** may be disposed on the upper pad **179**.

[0034] The upper semiconductor package **100B** may include a semiconductor chip **181**, a redistribution layer **183**, and a mold layer **185**. In an example embodiment, the upper semiconductor package **100B** may include a configuration identical or similar to the configuration of the lower semiconductor package **100A**. For example, the redistribution layer **183** may have the same configuration as the lower redistribution layer **150**.

[0035] FIG. 2 is an enlarged view of a portion A of FIG. 1. In FIG. 2, the portion A of FIG. 1 is shown in an inverted state such that the connecting terminal **160** is disposed at a higher level than

the lower redistribution layer **150**, for convenience of description. Accordingly, a constituent element referred to as a “top surface” in FIG. **1** may be referred to as a “bottom surface” in FIG. **2**, and a constituent element referred to as a “bottom surface” in FIG. **1** may be referred to as a “top surface” in FIG. **2**.

[0036] Referring to FIG. **2**, the connecting pad **139** may include a first top surface **139_U1**, a second top surface **139_U2**, and an inner side surface **139_S**. The second top surface **139_U2** may be disposed relatively farther from the die **131** of the semiconductor chip **130** than the first top surface **139_U1**. The first top surface **139_U1** may be disposed at a lower level than a top surface **137_U** of the second passivation layer **137** of the semiconductor chip **130** with reference to a top surface **131_U** of the die **131**, and the second top surface **139_U2** may be disposed at a higher level than the top surface **137_U** of the second passivation layer **137** of the semiconductor chip **130** with reference to the top surface **131_U** of the die **131**. The connecting pad **139** may have a step formed by the first top surface **139_U1** and the second top surface **139_U2**. The inner side surface **139_S** may interconnect the first top surface **139_U1** and the second top surface **139_U2**. The connecting pad **139** may include a recess **139_RC** defined by the first top surface **139_U1** and the inner side surface **139_S**.

[0037] The lower redistribution patterns CP may include a filled redistribution pattern and a conformal redistribution pattern. Each of the filled redistribution pattern and the conformal redistribution pattern may include a via extending through a lower insulating layer, and a conductive pattern on the via. The filled redistribution pattern may be formed by a fill plating process, and may completely fill an opening of the lower insulating layer, through which the via of the filled redistribution pattern extends. The via of the filled redistribution pattern may have a pillar shape. For example, the via of the filled redistribution pattern may have a tapered pillar shape. The conformal redistribution pattern may be formed by a conformal plating process, and may be formed in a uniform thickness along a side wall of the opening of the lower insulating layer, through which the via of the conformal redistribution pattern extends. The conformal redistribution pattern may include a recess.

[0038] The first lower redistribution pattern **153** may be a filled redistribution pattern formed by a fill plating process. The first lower redistribution pattern **153** may be referred to as a “first filled redistribution pattern”. The first lower redistribution pattern **153** may contact the first top surface **139_U1** of the connecting pad **139** while being spaced apart from the second top surface **139_U2** and the inner side surface **139_S** of the connecting pad **139**. The first lower pattern **153** may include a first via **153a** and a first conductive pattern **153b**. The first via **153a** may be disposed on the connecting pad **139**. A portion of the first via **153a** may be disposed in the recess **139_RC** of the connecting pad **139**. The first via **153a** may extend through the first lower insulating layer **151a**. A bottom surface of the first via **153a** may contact the first top surface **139_U1** of the connecting pad **139**. The width of the bottom surface of the first via **153a** may be smaller than the width of the first top surface **139_U1** of the connecting pad **139**. A side surface **153a_S** of the first via **153a** may be spaced apart from the inner side surface **139_S** of the connecting pad **139**. A portion of the first lower insulating layer **151a** may be interposed between the side surface **153a_S** of the first via **153a** and the inner side surface **139_S** of the connecting pad **139**. The first lower insulating layer **151a** may completely surround the side surface **153a_S** of the first via **153a**. The first lower insulating layer **151a** may contact a portion of the first top surface **139_U1** of the connecting pad **139**, and may contact the inner side surface **139_S** of the connecting pad **139**. The first lower insulating layer **151a** may fill the recess **139_RC** of the connecting pad **139**.

[0039] The first conductive pattern **153b** may be disposed on the first via **153a**. The first conductive pattern **153b** may completely cover a top surface of the first via **153a**. The width of the first conductive pattern **153b** may be greater than the width of the top surface of the first via **153a**. A portion of the first conductive pattern **153b** may not vertically overlap with the first via **153a**. A portion of the first conductive pattern **153b** may vertically overlap with a portion of the second top

surface **139_U2** of the connecting pad **139**. A minimum distance **H1** between a bottom surface **153b_B** of the first conductive pattern **153b** and the second top surface **139_U2** of the connecting pad **139** may be about 3 to 10 μm .

[0040] The second lower redistribution pattern **155** may be a filled redistribution pattern formed by a fill plating process. The second lower redistribution pattern **155** may be referred to as a “second filled redistribution pattern”. The second lower redistribution pattern **155** may include a second via **155a** and a second conductive pattern **155b**. The second via **155a** may be disposed on the first conductive pattern **153b**. The second via **155a** may extend through the second lower insulating layer **151b**. A bottom surface of the second via **155a** may contact a top surface of the first conductive pattern **153b**. The second conductive pattern **155b** may be disposed on the second via **155a**. The second conductive pattern **155b** may completely cover a top surface of the second via **155a**. A minimum distance **H2** between a bottom surface **155b_B** of the second conductive pattern **155b** and the top surface of the first conductive pattern **153b** may be equal to or greater than the minimum distance **H1** between a bottom surface **153_B** of the first conductive pattern **153b** and the second top surface **139_U2** of the connecting pad **139**.

[0041] The third lower redistribution pattern **157** may be a conformal redistribution pattern formed by a conformal plating process. The third lower redistribution pattern **157** may be referred to as a “conformal redistribution pattern” or a “first conformal redistribution pattern”. The third lower redistribution pattern **157** may have a uniform thickness. The third lower redistribution pattern **157** may include a third via **157a** and a third conductive pattern **157b**. The third via **157a** may extend through the third lower insulating layer **151c**. The third via **157a** may have a U shape. The third via **157a** may include a recess **157_RC**, and may include a top surface **157a_U** and an inner side surface **157a_S** which define the recess **157_RC**. The top surface **157a_U** of the third via **157a** may be disposed at a lower level than a top surface of the third lower insulating layer **151c** with reference to the top surface **131_U** of the die **131** of the semiconductor chip **130**. The inner side surface **157a_S** of the third via **157a** may interconnect the top surface **157a_U** of the third via **157a** and the third conductive pattern **157b**. The third conductive pattern **157b** may be connected to an upper end of the third via **157a**. The third conductive pattern **157b** may extend in the second direction **D2**, and an extension portion of the third conductive pattern **157b** may not overlap with the connecting pad **139**. The fourth lower insulating layer **151d** may cover the top surface **157a_U** and the inner side surface **139_S** of the third via **157a**. The fourth lower insulating layer **151d** may fill the recess **157_RC** of the third via **157a**. The fourth lower insulating layer **151d** may cover the third conductive pattern **157b**.

[0042] The UBM **159** may be connected to the third conductive pattern **157b** while extending through the fourth lower insulating layer **151d**. The UBM **159** may be disposed on the portion of the third conductive pattern **157b** extending in the second direction **D2**. The UBM **159** may not vertically overlap with the connecting pad **139**. The UBM **159** may not vertically overlap with the first lower redistribution pattern **153**, the second lower redistribution pattern **155**, and the third via **157a** of the third lower redistribution pattern **157**.

[0043] Although the lower redistribution patterns CP are shown in FIG. 2 as including two filled redistribution patterns **153** and **155**, the example embodiments of the disclosure are not limited thereto, and the lower redistribution patterns CP may include three or more filled redistribution patterns under the conformal redistribution pattern **157**. In an example embodiment, the lower redistribution patterns CP may further include a fourth lower redistribution pattern, which is a filled redistribution pattern, on the third lower redistribution pattern **157**.

[0044] FIG. 3 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0045] Referring to FIG. 3, lower redistribution patterns CP may include a first lower redistribution pattern **153**, a second lower redistribution pattern **155_1**, a third lower redistribution pattern **157_1**, and a fourth lower redistribution pattern **159_1**. Lower insulating layers **151** may include a first

lower insulating layer **151a**, a second lower insulating layer **151b**, a third lower insulating layer **151c**, a fourth lower insulating layer **151d**, and a fifth lower insulating layer **151e**. The first lower redistribution pattern **153** may be a filled redistribution pattern, and may have the same characteristics as the first lower redistribution pattern **153** described with reference to FIG. 2.

[0046] The second lower redistribution pattern **155_1** may be disposed on the first lower redistribution pattern **153**. The second lower redistribution pattern **155_1** may be a conformal redistribution pattern formed by a conformal plating process. The second lower redistribution pattern **155_1** may be referred to as a “first conformal redistribution pattern”. The second lower redistribution pattern **155_1** may have a uniform thickness. The second lower redistribution pattern **155_1** may include a second via **155a_1** and a second conductive pattern **155b_1**. The second via **155a_1** may extend through the second lower insulating layer **151b**. The second via **155a_1** may have a U shape. The second via **155a_1** may include a recess **155a_1RC**, and may include a top surface **155a_1U** and an inner side surface **155a_1S** which define the recess **155a_1RC**. The top surface **155a_1U** of the second via **155a_1** may be disposed at a lower level than a top surface of the second lower insulating layer **151b** with reference to a top surface **131_U** of a die **131** of a semiconductor chip **130**. The inner side surface **155a_1S** of the second via **155a_1** may interconnect the top surface **155a_1U** of the second via **155a_1** and the second conductive via **155b_1**. The second conductive pattern **155b_1** may be connected to an upper end of the second via **155a_1**. The third lower insulating layer **151c** may contact a portion of the top surface **155a_1U** of the second via **155a_1** and the inner side surface **155a_1S** of the second via **155a_1**. The third lower insulating layer **151c** may fill the recess **155a_1RC** of the second via **155a_1**. The third lower insulating layer **151c** may cover the second conductive pattern **155b_1**.

[0047] The third lower redistribution pattern **157_1** may be disposed on the second lower redistribution pattern **155_1**. The third lower redistribution pattern **157_1** may be a filled redistribution pattern formed by a fill plating process. The third lower redistribution pattern **157_1** may be referred to as a “second filled redistribution pattern”. A side surface of the third lower redistribution pattern **157_1** may be spaced apart from the inner side surface **155a_1S** of the second lower redistribution pattern **155_1**. The third lower insulating layer **151c** may be interposed between the side surface of the third lower redistribution pattern **157_1** and the inner side surface **155_1S** of the second lower redistribution pattern **155_1**. The third lower redistribution pattern **157_1** may include a third via **157a_1** and a third conductive pattern **157b_1**. The third via **157a_1** may extend through the third lower insulating layer **151c**. A portion of the third via **157a_1** may be disposed in the recess **155a_1RC** of the second via **155a_1**. A side surface **157a_1S** of the third via **157a_1** may be spaced apart from the inner side surface **155a_1S** of the second via **155a_1**. A portion of the top surface **155a_1U** of the second via **155a_1** may be exposed by the third via **157a_1**. The third insulating layer **151c** may fill the recess **155a_1RC** of the second via **155a_1**. The third lower insulating layer **151c** may contact the inner side surface **155a_1S** of the second via **155a_1**. The third lower insulating layer **151c** may contact a portion of the top surface **155a_1U** of the second via **155a_1** exposed by the third via **157a_1**. The third lower insulating layer **151c** may completely surround the side surface **157a_1S** of the third via **157a_1**. The third lower insulating layer **151c** may be disposed between the side surface **157a_1S** of the third via **157a_1** and the inner side surface **155a_1S** of the second via **155a_1**. The third conductive pattern **157b_1** may be disposed on the third via **157a_1**.

[0048] The fourth lower redistribution pattern **159_1** may be disposed on the third lower redistribution pattern **157_1**. The fourth lower redistribution pattern **159_1** may be a conformal redistribution pattern formed by a conformal plating process. The fourth lower redistribution pattern **159_1** may be referred to as a “second conformal redistribution pattern”. The fourth lower redistribution pattern **159_1** may include a fourth via **159a_1** and a fourth conductive pattern **159b_1**. The fourth via **159a_1** may extend through the fourth lower insulating layer **151d**. The fourth via **159a_1** may have a U shape. The fourth via **159a_1** may include a recess **159a_1RC**,

and may include a top surface **159a_1U** and an inner side surface **159a_1S** which define the recess **159a_1RC**. The top surface **159a_1U** of the fourth via **159a_1** may be disposed at a lower level than a top surface of the fourth lower insulating layer **151d** with reference to the top surface **131_U** of the die **131** of the semiconductor chip **130**. The inner side surface **159a_1S** of the fourth via **159a_1** may interconnect the top surface **159a_1U** of the fourth via **159a_1** and the fourth conductive pattern **159b_1**. The fourth conductive pattern **159b_1** may be connected to an upper end of the fourth via **159a_1**. The fifth insulating layer **151e** may be disposed on the fourth lower redistribution pattern **159_1**. The fifth lower insulating layer **151e** may contact the top surface **159a_1U** and the inner side surface **159a_1S** of the fourth via **159a_1**. The fifth lower insulating layer **151e** may fill the recess **159a_1RC** of the fourth via **159a_1**. A UBM **159** may be connected to the fourth lower redistribution pattern **159_1** while extending through the fifth lower insulating layer **151e**.

[0049] In an example embodiment, the fourth lower redistribution pattern **159_1** may be a filled redistribution pattern formed by a fill plating process, differently from the shown case. In an example embodiment, the fourth lower redistribution pattern **159_1** may be omitted, differently from the shown case. In this case, the third conductive pattern **157b_1** may be directly connected to the UBM **159**.

[0050] FIG. **4** is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0051] Referring to FIG. **4**, lower redistribution patterns CP may include a first lower redistribution pattern **153_2**, a second lower redistribution pattern **155_2**, and a third lower redistribution pattern **157_2**. Lower insulating layers **151** may include a first lower insulating layer **151a**, a second lower insulating layer **151b**, a third lower insulating layer **151c**, and a fourth lower insulating layer **151d**.

[0052] The first lower redistribution pattern **153_2** may be a conformal redistribution pattern formed by a conformal plating process. The first lower redistribution pattern **153_2** may be referred to as a “first conformal redistribution pattern”. The first lower redistribution pattern **153_2** may have a uniform thickness. The first lower redistribution pattern **153_2** may include a first via **153a_2** and a first conductive pattern **153b_2**. The first via **153a_2** may extend through the first lower insulating layer **151a**. The first via **153a_2** may have a U shape. A bottom surface of the first via **153a_2** may cover a first top surface **139_U1** of a connecting pad **139**. The width of the bottom surface of the first via **153a_2** may correspond to the width of a first top surface **139_U1** of the connecting pad **139**. A portion of an outer side surface **153a_20S** of the first via **153a_2** may contact an inner side surface **139_S** of the connecting pad **139**. A portion of the outer side surface **153a_20S** of the first via **153a_2** may contact the first lower insulating layer **151a**. The first via **153a_2** may include a recess **153a_2RC**, and may include a top surface **153a_2U** and an inner side surface **153a_2S** which define the recess **153a_2RC**. The top surface **153a_2U** of the first via **153a_2** may be disposed at a lower level than a second top surface **139_U2** of the connecting pad **139** with reference to a top surface **131_U** of a die **131** of a semiconductor chip **130**. The inner side surface **153a_2S** of the first via **153a_2** may interconnect the top surface **153a_2U** of the first via **153a_2** and the first conductive pattern **153b_2**. The first conductive pattern **153b_2** may be connected to an upper end of the first via **153a_2**. The second lower insulating layer **151b** may contact a portion of the top surface **153a_2U** of the first via **153a_2** and the inner side surface **153a_2S** of the first via **153a_2**. The second lower insulating layer **151b** may fill the recess **153a_2RC** of the first via **153a_2**. The second lower insulating layer **151b** may cover the first conductive pattern **153b_2**.

[0053] The second lower redistribution pattern **155_2** may be disposed on the first lower redistribution pattern **153_2**. The second lower redistribution pattern **155_2** may be a filled redistribution pattern formed by a fill plating process. The second lower redistribution pattern **155_2** may be referred to as a “first filled redistribution pattern”. A side surface of the second lower redistribution pattern **155_2** may be spaced apart from the inner side surface **153a_2S** of the first

lower redistribution pattern **153_2**. The second lower insulating layer **151b** may be interposed between the side surface of the second lower redistribution pattern **155_2** and the inner side surface **153a_2S** of the first lower redistribution pattern **153_2**. The second lower redistribution pattern **155_2** may include a second via **155a_2** and a second conductive pattern **155b_2**. The second via **155a_2** may extend through the second lower insulating layer **151b**. A portion of the second via **155a_2** may be disposed in the recess **153a_2RC** of the first via **153a_2**. A side surface **155a_2S** of the second via **155a_2** may be spaced apart from the inner side surface **153a_2S** of the first via **153a_2**. A bottom surface of the second via **155a_2** may contact a portion of the top surface **153a_2U** of the first via **153a_2**. A portion of the top surface **153a_2U** of the first via **153a_2** may be exposed by the second via **155a_2**. The second lower insulating layer **151b** may fill the recess **153a_2RC** of the first via **153a_2**. The second lower insulating layer **151b** may contact the inner side surface **153a_2S** of the first via **153a_2**. The second lower insulating layer **151b** may contact a portion of the top surface **153a_2U** of the first via **153a_2** exposed by the second via **155a_2**. The second lower insulating layer **151b** may completely surround the side surface **155a_2S** of the second via **155a_2**. The second lower insulating layer **151b** may be interposed between the side surface **155a_2S** of the second via **155a_2** and the inner side surface **153a_2S** of the first via **153a_2**. The second conductive pattern **155b_2** may be disposed on the second via **155a_2**. A portion of the second conductive pattern **155b_2** may vertically overlap with a portion of the first conductive pattern **153b_2**. A minimum distance **H2''** between the first conductive pattern **153b_2** and the second conductive pattern **155b_2** may be equal to or greater than a minimum distance **H1'** between the second top surface **139_U2** of the connecting pad **139** and the first conductive pattern **153b_2**. For example, the minimum distance **H1'** between the second top surface **139_U2** of the connecting pad **139** and the first conductive pattern **153b_2** may be about 3 to 10 μm .

[0054] The third lower redistribution pattern **157_2** may be disposed on the second lower redistribution pattern **155_2**. The third lower redistribution pattern **157_2** may be a conformal redistribution pattern formed by a conformal plating process. The third lower redistribution pattern **157_2** may be referred to as a “second conformal redistribution pattern”. The third lower redistribution pattern **157_2** may have a uniform thickness. The third lower redistribution pattern **157_2** may include a third via **157a_2** and a third conductive pattern **157b_2**. The third via **157a_2** may extend through the third lower insulating layer **151c**. The third via **157a_2** may have a U shape. The third via **157a_2** may include a recess **157a_2RC**, and may include a top surface **157a_2U** and an inner side surface **157a_2S** which define the recess **157a_2RC**. The top surface **157a_2U** of the third via **157a_2** may be disposed at a lower level than a top surface of the third lower insulating layer **151c** with reference to the top surface **131_U** of the die **131** of the semiconductor chip **130**. The inner side surface **157a_2S** of the third via **157a_2** may interconnect the top surface **157a_2U** of the third via **157a_2** and the third conductive via **157b_2**. The third conductive pattern **157b_2** may be connected to an upper end of the third via **157a_2**. The fourth lower insulating layer **151d** may be disposed on the third lower redistribution pattern **157_2**. The fourth lower insulating layer **151d** may fill the recess **157a_2RC** of the third via **157a_2**. The fourth lower insulating layer **151d** may contact the top surface **157a_2U** and the inner side surface **157a_2S** of the third via **157a_2**. The fourth lower insulating layer **151d** may cover the second conductive pattern **157b_2**.

[0055] FIG. 5 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0056] Referring to FIG. 5, lower redistribution patterns CP are different from the lower redistribution patterns CP of FIG. 4 in that a third lower redistribution pattern **157_2'** is a filled redistribution pattern other than a conformal redistribution pattern. The lower redistribution patterns CP of FIG. 5 may have the same characteristics as the lower redistribution patterns CP described with reference to FIG. 4, except that the third lower redistribution pattern **157_2'** is a filled redistribution pattern. The third lower redistribution pattern **157_2'** may be referred to as a

“second filled redistribution pattern”.

[0057] FIG. 6 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0058] Referring to FIG. 6, lower redistribution patterns CP may further include a fourth lower redistribution pattern **159_2**, as compared to the lower redistribution patterns CP of FIG. 5, and lower insulating layers **151** may further include a fifth lower insulating layer **151e**, as compared to the lower insulating layers **151** of FIG. 5. A third lower redistribution pattern **157_2''** may be spaced apart from a UBM **159**. The third lower redistribution pattern **157_2''** may include a third via **157a_2''** and a third conductive pattern **157b_2''**, and the third conductive pattern **157b_2''** may not lengthily extend in a second direction D2, differently from a third conductive pattern **157a_2'** of FIG. 5.

[0059] A fourth lower redistribution pattern **159_2** may be disposed on the third lower redistribution pattern **157_2''**. The fourth lower redistribution pattern **159_2** may be a conformal redistribution pattern formed by a conformal plating process. The fourth lower redistribution pattern **159_2** may be referred to as a “second conformal redistribution pattern”. The fourth lower redistribution pattern **159_2** may have a uniform thickness. The fourth lower redistribution pattern **159_2** may include a fourth via **159a_2** and a fourth conductive pattern **159b_2**. The fourth via **159a_2** may extend through a fourth lower insulating layer **151d**. The fourth via **159a_2** may have a U shape. The fourth via **159a_2** may include a recess **159a_2RC**, and may include a top surface **159a_2U** and an inner side surface **159a_2S** which define the recess **159a_2RC**. The top surface **159a_2U** of the fourth via **159a_2** may be disposed at a lower level than a top surface of the fourth lower insulating layer **151d** with reference to a top surface **131_U** of a die **131** of a semiconductor chip **130**. The inner side surface **159a_2S** of the fourth via **159a_2** may interconnect the top surface **159a_2U** of the fourth via **159a_2** and the fourth conductive pattern **159b_2**. The fourth conductive pattern **159b_2** may be connected to an upper end of the fourth via **159a_2**. The fourth conductive pattern **159b_2** may extend in the second direction D2, and an extension portion of the fourth conductive pattern **159b_2** may not overlap with a connecting pad **139**. The fifth lower insulating layer **151e** may cover the top surface **159a_2U** and the inner side surface **159a_2S** of the fourth via **159a_2**. The fifth lower insulating layer **151e** may fill the recess **159a_2RC** of the fourth via **159a_2**. The fifth lower insulating layer **151e** may cover the fourth conductive pattern **159b_2**.

[0060] A UBM **159** may be connected to the fourth conductive pattern **159b_2** while extending through the fifth lower insulating layer **151e**. The UBM **159** may be disposed on the portion of the fourth conductive pattern **159b_2** extending in the second direction D2.

[0061] In an example embodiment, the fourth lower redistribution pattern **159_2** may be a filled-plated pattern formed by a fill plating method, differently from the case shown in FIG. 6. In this case, the fourth lower redistribution pattern **159_2** may be referred to as a “third filled redistribution pattern”.

[0062] FIG. 7 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0063] Referring to FIG. 7, lower redistribution patterns CP may further include a fourth lower redistribution pattern **159_3**, as compared to the lower redistribution patterns CP of FIG. 4, and lower insulating layers **151** may further include a fifth lower insulating layer **151e**, as compared to the lower insulating layers **151** of FIG. 4.

[0064] A third lower redistribution pattern **157_3** may be disposed on a second lower redistribution pattern **155_2**. The third lower redistribution pattern **157_3** may be a conformal redistribution pattern formed by a conformal plating process. The third lower redistribution pattern **157_3** may be referred to as a “second conformal redistribution pattern”. The third lower redistribution pattern **157_3** may have a uniform thickness. The third lower redistribution pattern **157_3** may include a third via **157a_3** and a third conductive pattern **157b_3**. The third via **157a_3** may extend through a third lower insulating layer **151c**. The third via **157a_3** may have a U shape. The third via **157a_3**

may include a recess **157a_3RC**, and may include a top surface **157a_3U** and an inner side surface **157a_3S** which define the recess **157a_3RC**. The top surface **157a_3U** of the third via **157a_3** may be disposed at a lower level than a top surface of the third lower insulating layer **151c** with reference to a top surface **131_U** of a die **131** of a semiconductor chip **130**. The inner side surface **157a_3S** of the third via **157a_3** may interconnect the top surface **157a_3U** of the third via **157a_3** and the third conductive pattern **157b_3**. A fourth lower insulating layer **151d** may contact a portion of the top surface **157a_3U** of the third via **157a_3** and the inner side surface **157a_3S** of the third via **157a_3**.

[0065] The fourth lower redistribution pattern **159_3** may be disposed on the third lower redistribution pattern **157_3**. The fourth lower redistribution pattern **159_3** may be a filled redistribution pattern formed by a fill plating process. The fourth lower redistribution pattern **159_3** may be referred to as a “second filled redistribution pattern”. The fourth lower redistribution pattern **159_3** may include a fourth via **159a_3** and a fourth conductive pattern **159b_3**. The fourth via **159a_3** may extend through the fourth lower insulating layer **151d**, and a portion of the fourth via **159a_3** may be disposed in the recess **157a_3RC** of the third via **157a_3**. A side surface **159a_3S** of the fourth via **159a_3** may be spaced apart from the inner side surface **157a_3S** of the third via **157a_3**. A portion of the top surface **157a_3U** of the third via **157a_3** may be exposed by the fourth via **159a_3**. The fourth lower insulating layer **151d** may fill the recess **157a_3RC** of the third via **157a_3**. The fourth lower insulating layer **151d** may be interposed between the inner side surface **157a_3S** of the third via **157a_3** and the side surface **159a_3S** of the fourth via **159a_3**. The fourth lower insulating layer **151d** may contact the inner side surface **157a_3S** of the third via **157a_3**. The fourth lower insulating layer **151d** may contact a portion of the top surface **157a_3U** of the third via **157a_3** exposed by the fourth via **159a_3**. The fourth lower insulating layer **151d** may completely surround the side surface **159a_3S** of the fourth via **159a_3**. The fourth conductive pattern **159b_3** may be disposed on the fourth via **159a_3**. The fourth conductive pattern **159b_3** may extend in a second direction **D2**, and an extension portion of the fourth conductive pattern **159b_3** may not vertically overlap with a connecting pad **139**. The fifth lower insulating layer **151e** may cover the fourth conductive pattern **159b_3** of the fourth lower redistribution pattern **159_3**. A UBM **159** may be disposed on the extension portion of the fourth conductive pattern **159b_3** while extending through the fifth lower insulating layer **151e**.

[0066] FIG. 8 is a sectional view of a semiconductor package according to an example embodiment of the disclosure.

[0067] Referring to FIG. 8, a semiconductor package **100-1** may include a lower semiconductor package **100A** and an upper semiconductor package **100B**. The lower semiconductor package **100A** may include a semiconductor chip **130**, a mold layer **140_1**, a conductive connector **120_1**, a lower redistribution layer **150**, connecting terminals **160**, and an upper redistribution layer **171/CP_U1**. The lower semiconductor package **100A** of FIG. 8 is different from the lower semiconductor package **100A** of FIG. 1 in that the lower semiconductor package **100A** includes the mold layer **140_1** and the conductive connector **120_1**, which extends through the mold layer **140_1**, in place of the base layer **110** and the conductive connector **120_1**, respectively, in the base layer **110**.

[0068] The semiconductor chip **130** may be disposed on the lower redistribution layer **150**. The mold layer **140_1** may cover a side surface and a top surface of the semiconductor chip **130**. The mold layer **140_1** may cover a portion of a top surface of the lower redistribution layer **150**. The conductive connector **120_1** may extend through the mold layer **140_1**. The conductive connector **120_1** may electrically interconnect the lower redistribution layer **150** and the upper redistribution layer **171/CP_U1**.

[0069] The semiconductor chip **130** may have the same characteristics as the semiconductor chip **130** described with reference to FIG. 1, except that the semiconductor chip **130** includes a connecting pad **139** having a flat bottom surface. The lower redistribution layer **150** may include lower redistribution patterns **CP**, lower insulating layers **151**, and UBMs **159**, and the lower

redistribution patterns CP may have characteristics identical or similar to those of the lower redistribution patterns CP described with reference to FIGS. 1 to 7, except that the lower redistribution patterns CP are connected to the connecting pad 139 having the flat bottom surface. [0070] The upper redistribution layer 171/CP_U1 may be disposed on the mold layer 140_1. The upper redistribution layer 171/CP_U1 may include upper insulating layers 171 and upper redistribution patterns CP_U1, and the upper redistribution patterns CP_U1 may include a first upper redistribution pattern 173_1, a second upper redistribution pattern 175_1, and an upper pad 177_1 which are sequentially stacked. The upper insulating layers 171 may include a first upper insulating layer 171a, a second upper insulating layer 171b, and a third upper insulating layer 171c which are sequentially stacked. The first upper redistribution pattern 173_1 may be connected to the conductive connector 120_1 while extending through the first upper insulating layer 171a. The second upper redistribution pattern 175_1 may be connected to the first upper redistribution pattern 173_1 while extending through the second upper insulating layer 171b. The upper pad 177_1 may be disposed on the second upper redistribution pattern 175_1 in the third upper insulating layer 171c.

[0071] FIG. 9 is an enlarged view showing a portion of a semiconductor package according to an example embodiment of the disclosure.

[0072] Referring to FIG. 9, a connecting pad 139 of a semiconductor chip 130 may include a flat top surface 139_U. For example, the top surface 139_U of the connecting pad 139 may be coplanar with a top surface 137_U of a second passivation layer 137.

[0073] Lower redistribution patterns CP may be disposed on the connecting pad 139. The lower redistribution patterns CP may include a first lower redistribution pattern 153_2, a second lower redistribution pattern 155_2, and a third lower redistribution pattern 157_2. The first lower redistribution pattern 153_2 of FIG. 9 may be disposed on the top surface 139_U of the connecting pad 139. The first lower redistribution pattern 153_2 may be a conformal redistribution pattern formed by a conformal plating process. The first lower redistribution pattern 153_2 may include a first via 153a_2 and a first conductive pattern 153b_2. An outer side surface 153a_20S of the first via 153a_2 may be completely covered by a first lower insulating layer 151a. A minimum distance H1" between the top surface 139_U of the connecting pad 139 and the first conductive pattern 153b_2 may be about 3 to 10 μm . The first lower redistribution pattern 153_2 may have the same characteristics as the first lower redistribution pattern 153_2 described with reference to FIG. 4, except that the first lower redistribution pattern 153_2 is disposed on the flat top surface 139_U of the connecting pad 139, and the outer side surface 153a_20S of the first via 153a_2 is completely surrounded by the first lower insulating layer 151a. The second lower redistribution pattern 155_2 and the third lower redistribution pattern 157_2 may also have the same characteristics as the second lower redistribution pattern 155_2 and the third lower redistribution pattern 157_2 described with reference to FIG. 4.

[0074] FIG. 10 is a sectional view of a semiconductor package according to an example embodiment of the disclosure.

[0075] Referring to FIG. 10, a semiconductor package 100-2 may include a lower semiconductor package 100A and an upper semiconductor package 100B. The lower semiconductor package 100A may include a semiconductor chip 130, a mold layer 140_1, conductive connectors 120_1, a lower redistribution layer 150, connecting terminals 138 and 160, and an upper redistribution layer 171/CP_U1.

[0076] The semiconductor chip 130 may include a die 131 and chip pads 133. The chip pads 133 may be disposed on a bottom surface of the die 131. The mold layer 140_1 may cover the semiconductor chip 130. The mold layer 140_1 may cover a top surface of the lower redistribution layer 150. The conductive connectors 120_1 may extend through the mold layer 140_1, and thus may interconnect the lower redistribution layer 150 and the upper redistribution layer 171/CP_U1.

[0077] The lower redistribution layer 150 may be connected to the semiconductor chip 130 via the

connecting terminals **138**. The connecting terminals **138** may be disposed between the chip pads **133** of the semiconductor chip **130** and the lower redistribution layer **150**. The lower redistribution layer **150** may include lower insulating layers **151**, lower redistribution patterns CP, and UBMs **159**. The lower insulating layers **151** may include a first lower insulating layer **151a**, a second lower insulating layer **151b**, a third lower insulating layer **151c**, and a fourth lower insulating layer **151d**. The first to fourth lower insulating layers **151a**, **151b**, **151c** and **151d** may be sequentially stacked under the semiconductor chip **130** in a direction opposite to a first direction **D1**. Accordingly, the fourth lower insulating layer **151d**, which is an uppermost layer, may contact the mold layer **140_1**. The lower redistribution patterns CP may include a first lower redistribution pattern **153**, a second lower redistribution pattern **155**, a third lower redistribution pattern **157**, and a fourth lower redistribution pattern **158**. The first to fourth lower redistribution patterns **153**, **155**, **157** and **158** may be sequentially stacked in the direction opposite to the first direction **D1**. A portion of the first lower redistribution pattern **153** may extend through the first lower insulating layer **151a**. A portion of the first lower redistribution pattern **153** may be disposed on the first lower insulating layer **151a**. A portion of the second redistribution pattern **155** may be connected to the first lower redistribution pattern **153** while extending through the second lower insulating layer **151b**. A portion of the second lower redistribution pattern **155** may be disposed on the second lower insulating layer **151b**. A portion of the third lower redistribution pattern **157** may be connected to the second lower redistribution pattern **155** while extending through the third lower insulating layer **151c**. A portion of the third lower redistribution pattern **157** may be disposed on the third lower insulating layer **151c**. A portion of the fourth lower redistribution pattern **158** may be connected to the third lower redistribution pattern **157** while extending through the fourth lower insulating layer **151d**. A portion of the fourth lower redistribution pattern **158** may be disposed on the fourth lower insulating layer **151d**. The fourth lower redistribution pattern **158** may be connected to the connecting terminal **138**, and thus may be electrically connected to the semiconductor chip **130** via the connecting terminal **138**. The fourth lower redistribution pattern **158** may contact the mold layer **140_1**. The UBMs **159** may be disposed in the first lower insulating layer **151a**. The UBMs **159** may be connected to the first lower redistribution pattern **153**. The first lower redistribution pattern **153** may be connected to top surfaces of the UBMs **159**. Bottom surfaces of the UBMs **159** may be exposed by the first lower insulating layer **151a**. Connecting terminals **160** may be disposed on the bottom surfaces of the UBMs **159**.

[0078] One or two of the first to fourth lower redistribution patterns **153**, **155**, **157** and **158** may be a conformal redistribution pattern formed by a conformal plating process, and the remaining three or two of the first to fourth lower redistribution patterns **153**, **155**, **157** and **158** may be a filled redistribution pattern formed by a fill plating process. The lower redistribution patterns CP of FIG. **10** may include the first to third lower redistribution patterns **153**, **155** and **157**, and may not include the fourth lower redistribution pattern **158**. In this case, the lower insulating layers **151** may include the first to third insulating layers **151a**, **151b** and **151c**, and may not include the fourth lower insulating layer **151d**. The lower redistribution patterns CP of FIG. **10** may have the characteristics of the lower redistribution patterns CP described with reference to FIGS. **2** to **7**. The lower redistribution patterns CP of FIG. **10** may be different from the lower redistribution patterns CP of FIGS. **2** to **7** only in that the first lower redistribution pattern **153** contacts the UBMs **159** other than the connecting pad **139**, the third lower redistribution pattern **157** or the fourth lower redistribution pattern **158** contacts the connecting terminals **138** other than the UBMs **159**.

[0079] FIG. **11** is an enlarged view of a portion of a semiconductor package according to an example embodiment of the disclosure.

[0080] Referring to FIG. **11**, a UBM **159** may be disposed in a first lower insulating layer **151a**. A bottom surface of the UBM **159** may be coplanar with a bottom surface of the first lower insulating layer **151a**. A connecting terminal **160** may be disposed on the bottom surface of the UBM **159**.

[0081] Lower redistribution patterns CP may include a first lower redistribution pattern **153_2**, a

second lower redistribution pattern **155_2**, a third lower redistribution pattern **157_2**, and a fourth lower redistribution pattern **158**. The first lower redistribution pattern **153_2** may be disposed on the UBM **159** disposed in the first lower insulating layer **151a**. The first lower redistribution pattern **153_2** may be a conformal redistribution pattern formed by a conformal plating process. The first lower redistribution pattern **153_2** may include a first via **153a_2** and a first conductive pattern **153b_2**. An outer side surface **153a_20S** of the first via **153a_2** may completely contact the first lower insulating layer **151a**. A minimum distance $H1''$ between the UBM **159** and the first conductive pattern **153b_2** may be about 3 to 10 μm . The first lower redistribution pattern **153_2** may have the same characteristics as the first lower redistribution pattern **153_2** described with reference to FIG. 4, except that the first lower redistribution pattern **153_2** is disposed on the UBM **159** such that the outer side surface **153a_20S** of the first via **153a_2** is completely surrounded by the first lower insulating layer **151a**. Further, the second lower redistribution pattern **155_2** and the third lower redistribution pattern **157_2** may have the same characteristics as the second lower redistribution pattern **155_2** and the third lower redistribution pattern **157_2** described with reference to FIG. 4. The fourth lower redistribution pattern **158** may be disposed on the third lower redistribution pattern **157_2**, and may be a filled redistribution pattern or a conformal redistribution pattern. The fourth lower redistribution pattern **158** may include a fourth via **158a** and a fourth conductive pattern **158b**. The fourth via **158a** may be connected to the third lower redistribution pattern **157_2** while extending through the fourth lower insulating layer **151d**. The fourth conductive pattern **158b** may be disposed on the fourth via **158a**, and may be connected to the connecting terminal **160**.

[0082] In accordance with the example embodiments of the disclosure, a redistribution layer having a stack via structure, in which a plurality of vias is vertically stacked, may include a filled redistribution pattern and a conformal redistribution pattern, and thus may alleviate stress caused by a coefficient of thermal expansion difference between a semiconductor chip and the stack via structure. Accordingly, a semiconductor package having enhanced reliability may be provided.

[0083] While the above example embodiments of the disclosure have been described with reference to the accompanying drawings, it should be understood by those skilled in the art that various modifications may be made without departing from the scope of the disclosure and without changing essential features thereof. Therefore, the above-described example embodiments should be considered in a descriptive sense only and not for purposes of limitation.

Claims

1. A semiconductor package comprising: a lower redistribution layer; a semiconductor chip on the lower redistribution layer, the semiconductor chip comprising a connecting pad; a mold layer covering the semiconductor chip on the lower redistribution layer; and a conductive connector penetrating the mold layer and disposed on one side of the semiconductor chip, a side surface of the conductive connector being surrounded by the mold layer, wherein the lower redistribution layer comprises: a first lower insulating layer, a first conformal redistribution pattern extending through the first lower insulating layer, the first conformal redistribution pattern including a first top horizontal portion, a first bottom horizontal portion, and a first connecting portion interconnecting the first top horizontal portion and the first bottom horizontal portion, a second lower insulating layer on the first lower insulating layer and the first conformal redistribution pattern, and a first filled redistribution pattern on the first conformal redistribution pattern, the first filled redistribution pattern extending through the second lower insulating layer, the first filled redistribution pattern including a first via and a first conductive pattern, the first via being a filled pattern extending through the second lower insulating layer, an entirety of a top surface of the first via being in contact with the first conductive pattern, the first conductive pattern extending horizontally on the second lower insulating layer, wherein a side surface of the first filled

redistribution pattern is spaced apart from an inner side surface of the first connecting portion of the first conformal redistribution pattern, and wherein the second lower insulating layer is between the inner side surface of the first connecting portion of the first conformal redistribution pattern and the side surface of the first filled redistribution pattern.

2. The semiconductor package according to claim 1, further comprising: an upper redistribution layer on the mold layer, and wherein the conductive connector electrically connects the lower redistribution layer and the upper redistribution layer.

3. The semiconductor package according to claim 1, wherein: the first conformal redistribution pattern defines a first recess, and the second lower insulating layer fills the first recess and contacts an upper surface of the first bottom horizontal portion of the first conformal redistribution pattern.

4. The semiconductor package according to claim 3, wherein the second lower insulating layer completely covers the inner side surface of the first connecting portion of the first conformal redistribution pattern.

5. The semiconductor package according to claim 3, wherein: a side surface of the first via of the first filled redistribution pattern is spaced apart from the side surface of the first connecting portion of the first conformal redistribution pattern.

6. The semiconductor package according to claim 5, wherein: the second lower insulating layer completely surrounds the side surface of the first via of the first filled redistribution pattern.

7. The semiconductor package according to claim 1, wherein: the first bottom horizontal portion of the first conformal redistribution pattern contacts the connecting pad.

8. The semiconductor package according to claim 7, wherein a first minimum distance between a lower surface of the first top horizontal portion of the first conformal redistribution pattern and an upper surface of the connecting pad is about 3 to 10 μm .

9. The semiconductor package according to claim 8, wherein a second minimum distance between an upper surface of the first top horizontal portion of the first conformal redistribution pattern and a lower surface of the first conductive pattern is substantially equal to or greater than the first minimum distance.

10. The semiconductor package according to claim 1, further comprising: a third lower insulating layer on the second lower insulating layer; and a second conformal redistribution pattern being on the first filled redistribution pattern and extending through the third lower insulating layer, the second conformal redistribution pattern including a second top horizontal portion, a second bottom horizontal portion, and a second connecting portion interconnecting the second top horizontal portion and the second bottom horizontal portion.

11. The semiconductor package according to claim 10, further comprising: a fourth lower insulating layer on the third lower insulating layer and the second conformal redistribution pattern, and wherein the second conformal redistribution pattern defines a second recess, and the fourth lower insulating layer fills the second recess and contacts an entirety of an upper surface of the second bottom horizontal portion of the second conformal redistribution pattern.

12. The semiconductor package according to claim 10, further comprising: a fourth lower insulating layer on the third lower insulating layer and the second conformal redistribution pattern; and a second filled redistribution pattern being on the second conformal redistribution pattern and extending through the fourth lower insulating layer, the second filled redistribution pattern including a second via and a second conductive pattern, the second via being a filled pattern extending through the fourth lower insulating layer, an entirety of a top surface of the second via being in contact with the second conductive pattern, the second conductive pattern extending horizontally on the fourth lower insulating layer.

13. The semiconductor package according to claim 12, wherein: a side surface of the second filled redistribution pattern is spaced apart from an inner side surface of the second connecting portion of the second conformal redistribution pattern, and the fourth lower insulating layer is between the inner side surface of the second connecting portion of the second conformal redistribution pattern

and the side surface of the second filled redistribution pattern.

14. The semiconductor package according to claim 13, wherein: the second conformal redistribution pattern defines a second recess, the fourth lower insulating layer fills the second recess and contacts an upper surface of the first bottom horizontal portion of the first conformal redistribution pattern, and a side surface of the second via of the second filled redistribution pattern is spaced apart from a side surface of the second connecting portion of the second conformal redistribution pattern.

15. A semiconductor package comprising: a lower redistribution layer; a semiconductor chip on the lower redistribution layer; a mold layer covering the semiconductor chip on the lower redistribution layer; and a conductive connector penetrating the mold layer and disposed on one side of the semiconductor chip, a side surface of the conductive connector being surrounded by the mold layer; wherein the semiconductor chip comprises a die, a chip pad on the die, and a connecting pad on the chip pad, wherein the lower redistribution layer comprises: a first lower insulating layer covering the connecting pad, a first conformal redistribution pattern extending through the first lower insulating layer, the first conformal redistribution pattern including a top horizontal portion, a bottom horizontal portion, and a connecting portion interconnecting the top horizontal portion and the bottom horizontal portion, a second lower insulating layer on the first lower insulating layer and the first conformal redistribution pattern, and a first filled redistribution pattern on the first conformal redistribution pattern, the first filled redistribution pattern extending through the second lower insulating layer, the first filled redistribution pattern including a via and a conductive pattern, the via being a filled pattern extending through the second lower insulating layer, an entirety of a top surface of the via being in contact with the conductive pattern, the conductive pattern extending horizontally on the second lower insulating layer, wherein an outer surface of the connecting portion of the first conformal redistribution pattern is surrounded by the first lower insulating layer, wherein a side surface of the first filled redistribution pattern is spaced apart from an inner side surface of the connecting portion of the first conformal redistribution pattern, and wherein the second lower insulating layer is between the inner side surface of the connecting portion of the first conformal redistribution pattern and the side surface of the first filled redistribution pattern.

16. The semiconductor package according to claim 15, wherein: an upper surface of the connecting pad is substantially coplanar, and the bottom horizontal portion of the first conformal redistribution pattern contacts the upper surface of the connecting pad.

17. The semiconductor package according to claim 15, wherein: a maximum thickness of the second lower insulating layer is greater than a maximum thickness of the first lower insulating layer.

18. The semiconductor package according to claim 15, wherein: the connecting portion and the bottom horizontal portion of the first conformal redistribution pattern defines a recess, and the second lower insulating layer fills the recess and contacts an inner side surface of the connecting portion of the first conformal redistribution pattern.

19. The semiconductor package according to claim 18, wherein: the second lower insulating layer completely surrounds the side surface of the first filled redistribution pattern.

20. A semiconductor package comprising: a semiconductor chip comprising a connecting pad; a mold layer covering the semiconductor chip; a lower redistribution layer on a bottom surface of the mold layer; and a conductive connector connected to the lower redistribution layer and extending through the mold layer, wherein the lower redistribution layer comprises: a first lower insulating layer, a first conformal redistribution pattern extending through the first lower insulating layer, the first conformal redistribution pattern including a top horizontal portion, a bottom horizontal portion, and a connecting portion interconnecting the top horizontal portion and the bottom horizontal portion, a second lower insulating layer on the first lower insulating layer and the first conformal redistribution pattern, and a first filled redistribution pattern on the first conformal redistribution pattern, the first filled redistribution pattern extending through the second lower

insulating layer, the first filled redistribution pattern including a via and a conductive pattern, the via being a filled pattern extending through the second lower insulating layer, an entirety of a top surface of the via being in contact with the conductive pattern, the conductive pattern extending horizontally on the second lower insulating layer, wherein the connecting portion and the bottom horizontal portion of the first conformal redistribution pattern defines a recess, wherein the via of the first filled redistribution pattern fills a portion of the recess and contacts the bottom horizontal portion of the first conformal redistribution pattern, and wherein the second lower insulating layer fills the remaining portion of the recess, and an inner surface of the connection portion of the first conformal redistribution pattern is spaced apart from an outer surface of the via of the first filled redistribution pattern by the second lower insulating layer.
