

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250286020

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Ho; Kai-Kuang et al.

SEMICONDUCTOR BONDING STRUCTURE

Abstract

The present disclosure relates to a semiconductor package, a semiconductor bonding structure and a method of fabricating the same. The semiconductor package includes a first chip, a second chip and a conductive structure, wherein the conductive structure is disposed at a side of the second chip and over a second upper surface of the first interconnection structure to electrically connect to the first interconnection structure. The semiconductor bonding structure includes a first substrate, a plurality of first interconnection structures, a plurality of chips and a plurality of conductive structures, wherein the conductive structures are respectively disposed at a side of each of the chips and over a second upper surface of each first interconnection structure, to electrically connect to each first interconnection.

Inventors: Ho; Kai-Kuang (Hsinchu City, TW), Lin; Ju-Jie (Taichung City, TW), Hsu; Yi-Feng (Hsinchu City, TW)

Applicant: UNITED MICROELECTRONICS CORP. (Hsin-Chu City, TW)

Family ID: 90573493

Assignee: UNITED MICROELECTRONICS CORP. (Hsin-Chu City, TW)

Appl. No.: 19/215306

Filed: May 21, 2025

Foreign Application Priority Data

TW

111138340

Oct. 11, 2022

Related U.S. Application Data

parent US continuation 17989635 20221117 PENDING child US 19215306

Publication Classification

Int. Cl.: H01L25/065 (20230101); H01L23/00 (20060101); H01L23/31 (20060101)

U.S. Cl.:

CPC H01L25/0657 (20130101); H01L23/3107 (20130101); H01L24/08 (20130101); H01L24/16 (20130101); H01L2224/02371 (20130101); H01L2224/0401 (20130101); H01L2224/08145 (20130101); H01L2224/16225 (20130101)

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS [0001] This application is a continuation application of U.S. application Ser. No. 17/989,635, filed on Nov. 17, 2022. The content of the application is incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present disclosure relates to a semiconductor technology, and more particularly, to a semiconductor package, a semiconductor bonding structure and a method of fabricating the same.

2. Description of the Prior Art

[0004] In advanced semiconductor industry, integration density of various electronic components has been continuously improved by reducing minimum feature size, which allows more electronic components to be integrated into given areas. These smaller electronic components also require smaller packages that utilize less area than the conventional packages.

[0005] Three dimensional integrated circuits (3DICs) refer to a three-dimensional stack of chips formed by using wafer-level bonding and through-silicon-via (TSV) technologies. In comparison with conventional two-dimensional chips, the 3DICs may have the advantages of using the space more effectively, shorter signal transmission distances between chips, and lower interconnecting resistances. The 3DICs have gradually become the mainstream technology of power converters, low noise amplifiers, radio frequency (RF) or millimeter wave (MMW) components. Furthermore, the 3DICs may also be achieved by placing chips over chips of a wafer-level, or forming a bonding interface between the chips by a hybrid bonding process. The hybrid bonding (also known as “metal/dielectric hybrid bonding”) may be a direct bonding technology without using intermediate layers like solder bond or adhesives, which obtains metal-to-metal bonding and dielectric-to-dielectric bonding simultaneously, so as to overcome the fabrication limits of the micro bump technology.

[0006] However, the current 3DICs still have problems need to be further improved to meet the semiconductor industrial requirements.

SUMMARY OF THE INVENTION

[0007] In light of the above, the present disclosure is directed to provide a semiconductor package, a semiconductor bonding structure, and a method of fabricating the same, in which the semiconductor package is fabricated by copper-to-copper direct bonding in a chip-to-wafer bonding manner, and the chip and a conductive structure are respectively bonded to two different upper surfaces of an interconnection structure the of wafer. Accordingly, the copper-to-copper direct bonding is not only capable to replace the conventional through-silicon-via (TSV) structure, simplifying the fabricating complexity and cost of the TSV, but also improves the structural defects possibly derived from the TSV structure. Therefore, the present disclosure is allowable to form the semiconductor package with more reliable structure under a simplified fabricating process, with the

conductive structure being disposed at a location higher than the chip, so as to facilitate the arrangements of input/output terminals in the subsequent fabricating processes.

[0008] According to an embodiment of the present disclosure, a semiconductor package is provided and includes a first chip, a second chip, and a conductive structure. The first chip includes a first substrate and a first interconnection structure disposed on the first substrate, wherein an upper surface of the first interconnection structure includes a first upper surface and a second upper surface. The second chip is stacked on the first chip, and the second chip includes a second substrate and a second interconnection structure disposed on the second substrate, wherein the second interconnection structure directly and electrically connects to the first upper surface of the first interconnection structure. The conductive structure is disposed at one side of the second chip, on the second upper surface of the first interconnection structure, and the conductive structure electrically connects to the first interconnection structure.

[0009] According to an embodiment of the present disclosure, a semiconductor bonding structure is provided and includes a primary substrate, a plurality of first interconnection structures, a plurality of chips, and a plurality of conductive structures. The plurality of first interconnection structures is disposed on the primary substrate, wherein an upper surface of each of the first interconnection structures includes a first upper surface and a second upper surface. The plurality of chips is disposed on the first interconnection structures and electrically connects to the first interconnection structures respectively, and each of the chips includes a substrate and a second interconnection structure disposed on the substrate, wherein the second interconnection structure directly and electrically connects to the first upper surface of each of the first interconnection structures. The plurality of conductive structures is disposed at one side of each of the chips, on the second upper surface of each of the first interconnection structures, and the conductive structures electrically connects to the first interconnection structures respectively.

[0010] According to an embodiment of the present disclosure, a method of forming a semiconductor bonding structure is provided and includes the following steps. Firstly, a first semiconductor structure is formed, wherein the first semiconductor structure includes a first substrate and a first interconnection structure disposed on the first substrate, and an upper surface of the first interconnection structure comprises a first upper surface and a second upper surface. Next, a second semiconductor structure is formed, wherein the second semiconductor structure includes at least one chip, and the second semiconductor structure is bonded to the first upper surface of the first interconnection structure of the first semiconductor structure. Then, at least one conductive structure is formed at one side of the second semiconductor structure, on the second upper surface of the first interconnection structure to electrically connect to the first interconnection structures.

[0011] These and other objectives of the present invention will no doubt become obvious to those of ordinary skill in the art after reading the following detailed description of the preferred embodiment that is illustrated in the various figures and drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] FIG. 1 to FIG. 6 illustrate schematic diagrams of a fabricating method of a semiconductor bonding structure and a semiconductor package according to a first embodiment of the present disclosure, in which:

[0013] FIG. 1 is a schematic cross-sectional view of a semiconductor bonding structure after forming an interconnection structure;

[0014] FIG. 2 is a schematic cross-sectional view of a semiconductor bonding structure after forming and bonding to a chip;

[0015] FIG. **3** is a schematic cross-sectional view of a semiconductor bonding structure after forming a covering layer;

[0016] FIG. **4** is a schematic cross-sectional view of a semiconductor bonding structure after forming a molding layer and openings;

[0017] FIG. **5** is a schematic cross-sectional view of a semiconductor bonding structure after forming a conductive structure; and

[0018] FIG. **6** is a schematic cross-sectional view of a semiconductor bonding structure after forming the semiconductor package.

[0019] FIG. **7** to FIG. **8** illustrate schematic diagrams of a fabricating method of a semiconductor bonding structure and a semiconductor package according to a second embodiment of the present disclosure, in which:

[0020] FIG. **7** is a schematic cross-sectional view of a semiconductor bonding structure after forming a conductive structure; and

[0021] FIG. **8** is a schematic cross-sectional view of a semiconductor bonding structure after forming the semiconductor package.

[0022] FIG. **9** to FIG. **11** illustrate schematic diagrams of a fabricating method of a semiconductor bonding structure and a semiconductor package according to a third embodiment of the present disclosure, in which:

[0023] FIG. **9** is a schematic cross-sectional view of a semiconductor bonding structure after forming a protection layer;

[0024] FIG. **10** is a schematic cross-sectional view of a semiconductor bonding structure after forming a conductive structure; and

[0025] FIG. **11** is a schematic cross-sectional view of a semiconductor bonding structure after forming the semiconductor package.

[0026] FIG. **12** illustrates a schematic diagram of a fabricating method of a semiconductor bonding structure according to a fourth embodiment of the present disclosure.

DETAILED DESCRIPTION

[0027] To provide a better understanding of the presented disclosure, preferred embodiments will be described in detail. The preferred embodiments of the present disclosure are illustrated in the accompanying drawings with numbered elements. In addition, the technical features in different embodiments described in the following may be replaced, recombined, or mixed with one another to constitute another embodiment without departing from the spirit of the present disclosure.

[0028] Please refer to FIG. **1** to FIG. **6**, which illustrate schematic diagrams of a fabricating method of a semiconductor bonding structure and a semiconductor package according to the first embodiment of the present disclosure. Firstly, as shown in FIG. **1**, a semiconductor structure such as a wafer-level semiconductor structure is provided, and which includes a primary substrate **100** and at least one interconnection structure **106**. The primary substrate **100** for example includes a silicon substrate, an epitaxial silicon substrate, a silicon-containing substrate such as a SiC substrate or a SiGe substrate, a group III-V semiconductor substrate or a substrate including any suitable material, and the primary substrate **100** has two surfaces **102**, **104** opposite disposed to each other.

[0029] In the present embodiment, a plurality of interconnection structures **106** are formed on the surface **104** of the primary substrate **100**, with the interconnection structures **106** being directly adjacent to each other and respectively disposed within a plurality of die regions (not shown in the drawings) on the primary substrate **100**, wherein each of the die regions may include various types of wafers or are expected to provide various functions, for example being used as a display driver integrated circuit (DDIC), a radio frequency (Rf), a dynamic random access memory (DRAM), a static random access memory (SRAM), or a driver circuit, but is not limited thereto. Each of the interconnection structures **106** includes a plurality of sequentially stacked dielectric layers (not shown in the drawings) and a plurality of conductive layers (not shown in the drawings) disposed

in each of the dielectric layers, wherein the dielectric layers for example include a dielectric material such as silicon oxide, silicon nitride, silicon oxynitride or silicon carbonitride, and the conductive layers for example includes a low resistant metal material like copper (Cu), aluminum (Al), tungsten (W) or titanium (Ti), and preferably includes copper, but is not limited thereto. [0030] It is noted that, each of the interconnection structures **106** further includes at least one bonding pad **108**, **109** embedded in the interconnection structure **106**, so that, the surfaces of the bonding pads **108**, **109** are respectively exposed from an upper surface **106a** and an upper surface **106b** of each interconnection structure **106**. The upper surface **106a** and the upper surface **106b** may be optionally coplanar with each other, and both disposed on a top surface of the interconnection structure **106**, but not limited thereto. In another embodiment, the surfaces of the bonding pads **108**, **109** may also be respectively exposed from two upper surfaces which are not coplanar with each other, due to practical product requirements. Also, although the present embodiment is exemplified by disposing one bonding pads **108** at two opposite sides of the bonding pads **109** respectively, people well-skilled in the art should fully realized that the practical disposing number and the disposing locations of the bonding pads **108** and/or the bonding pads **109** are not limited to what is shown in FIG. 1, and which may be further adjusted based on practical requirements.

[0031] Next, another semiconductor structure such as a semiconductor structure which is also a wafer-level semiconductor structure is provided, and which includes a primary substrate **200** (for example including a silicon substrate, an epitaxial silicon substrate, a silicon-containing substrate, or a group III-V semiconductor substrate) having two opposite surfaces **202**, **204**, and at least one interconnection structure **206**. In the present embodiment, a plurality of interconnection structures **206** are also formed on the surface **204** of the primary substrate **200**, with the interconnection structures **206** being directly adjacent to each other and respectively disposed within a plurality of die regions (not shown in the drawings) on the primary substrate **200**, wherein each of the interconnection structures **206** also includes a plurality of sequentially stacked dielectric layers (not shown in the drawings) and a plurality of conductive layers (not shown in the drawings) disposed in each of the dielectric layers. The material selections of the dielectric layers and the conductive layers of the interconnection structures **206** are substantially the same as that of the interconnection structures **106**, and which will not be redundant described hereinafter. Also, people well-skilled in the art should fully realized that the practical disposing number of the interconnection structures **106** and/or the interconnection structures **206** are not limited to what is shown in FIG. 1, and which may be further adjusted according to the practical require number of the die regions in a device.

[0032] In the present embodiment, the another semiconductor structure further includes a plurality of scribe lines **208** at the junctions of the die regions of the primary substrate **200** respectively, so that, the primary substrate **200** and the plurality of the interconnection structures **206** of the another semiconductor structure may be cut into a plurality of chips **210** as shown in FIG. 2 through the scribe lines **208**, in the subsequent die saw process. It is noted that, each of the chips **210** includes a substrate **200a** and the interconnection structure **206** disposed on the surface **204** of the substrate **200a**.

[0033] As shown in FIG. 2, the semiconductor structure and the chips **210** are placed on a machine (not shown in the drawings) capable of performing a die bonding process, for bonding the chips **210** to the semiconductor structure. In the present embodiment, the die bonding process is carried by attaching and bonding the interconnection structure **206** of each of the chips **210** to the upper surfaces **106b** of each of the interconnection structures **106** on the semiconductor structure, and exposing the two upper surfaces **106a** (namely, the surfaces of the bonding pads **108**) at both two sides of the upper surface **106b**. With these arrangements, at least one conductive layer of each of the interconnection structures **206** may directly contact the bonding pads **109** of each of the interconnection structures **106**, and the chips **210** are electrically connected with the semiconductor structure. Furthermore, in the present embodiment, a wafer thinning process such as a chemical

mechanical polishing (CMP) process or an etching process may be optionally performed on the surface **202** of the primary substrate **200**, before performing the die saw process, to reduce the overall thickness of the primary substrate **200** and to form a surface **202a**. People well-skilled in the art should fully realized that the reduced thickness of the substrate by the wafer thinning process may be adjusted according to the practical process requirements, so as to avoid the possible structural defects caused by excessive increasing of the overall thickness after forming a molding layer in the subsequent process. Also, the heat dissipation efficiency of the substrate **200a** may be enhanced thereby through reducing the overall thickness of the substrate.

[0034] As shown in FIG. **3**, a covering layer **110** is formed on the upper surfaces **106a** of each of the interconnection structure **106**, to cover the surfaces of the bonding pads **108**. Precisely speaking, a deposition process such as a redox deposition process, or an electroplating process such as electroless plating or chemical plating is performed to form the covering layer **110** on the bonding pads **108**, at both two sides of each of the chips **210**, thereby preventing from the metal oxidation of the bonding pads **108**. In the present embodiment, the covering layer **110** for example includes a conductive material with protective capability, such as a metal material that is not easily oxidized, such as tin (Sn), gold (Au), palladium (Pd), nickel (Ni) and silver (Ag), and preferably to solder bond, but not limited thereto. In another embodiment, the covering layer may also include a non-conductive material with protective capability.

[0035] As shown in FIG. **4**, a molding layer **112** is formed on the semiconductor structure and the chips **210**, to cover the chips **210** and the first interconnection structures **106** of the semiconductor structure, so as to overall perform like a wafer-level semiconductor structure. Precisely speaking, the molding layer **112** includes a plurality of openings **114**, and each of the openings **114** is in alignment with each of the bonding pads **108** underneath, thereby exposing the covering layer **110** covered on each of the bonding pads **108** through each opening **114**. In one embodiment, the formation of the openings **114** is accomplished for example through a photolithography and etching process, a dry etching process or a laser burning process. Preferably, the laser burning process is performed by using the covering layer **110** as a stop layer, so as to save the fabricating cost, but not limited thereto.

[0036] As shown in FIG. **5**, at least one conductive structure is formed on the semiconductor structure. In the present embodiment, the conductive structure for example includes at least one solder pillar **116** at least filled up the openings **114** as shown in FIG. **4**, wherein the solder pillars **116** for example include a material like tin, gold, or palladium, but is not limited thereto. In a preferably embodiment, the solder pillars **116** may include the same material as the covering layer **110**, such as solder bond, so that, the solder pillars **116** may therefore be formed by a reflow soldering process. Accordingly, the solder pillars **116** and the covering layer **110** underneath may be monolithic, but is not limited thereto. It is noted that, the solder pillars **116** is partially disposed within the molding layer **112**, and is partially protruded from the top surface of the molding layer **112**, so that, the bottom of the solder pillars **116** may contact the bonding pads **108** directly or through the covering layer **110**, to electrically connect with the interconnection structures **106**, and the top of the solder pillars **116** is protruded from the molding layer **112**, for conveniently arranging the input/output terminals (I/O) in the subsequent processes.

[0037] After that, the primary substrate **100** and the plurality of the interconnection structures **106** of the semiconductor structure are cut into a plurality of chips **120** as shown in FIG. **6** through a plurality of scribe lines **118** at the junctions of the die regions in the primary substrate **100** respectively, in the subsequent die saw process, wherein, each of the chips **120** includes a substrate **100a** and the interconnection structure **106** disposed on the surface **104** of the substrate **100a**. Meanwhile, a plurality of semiconductor packages **300** as shown in FIG. **6** is formed thereby. Through the aforementioned processes, the fabricating method the of semiconductor bonding structure and the semiconductor package of the first embodiment in the present disclosure is accomplished. Following these, the subsequent packaging process may be further performed on the

semiconductor package **300**, for example further mounting the semiconductor package **300** to a circuit board (not shown in the drawings) or other secondary packaging substrates via the solder pillars **116** disposed thereon, to form the required integrated circuits. Alternatively, the semiconductor package **300** may also be used directly as a chip scale package (CSP) of the wafer-level package, which is beneficial on thin and short packaging application.

[0038] As shown in FIG. **6**, the semiconductor package **300** obtained by the fabricating method of the present embodiment includes the chip **120**, the chip **210** stacked on the chip **120**, and the conductive structure (such as the solder pillars **116**), wherein the chip **210** is electrically connected to the chip **120** by directly contacting the upper surfaces **106b** of the interconnection structure **106** through the interconnection structure **206** disposed on the chip **210**, so that, the additional arrangement of a TSV is no longer needed. In particular, the solder pillars **116** disposed on the upper surfaces **106a** of the interconnection structure **106** on the chip **120** is configured as the conductive structure of the present embodiment, and which is disposed at one side of the chip **210** and electrically connects the bonding pads **108** embedded in the interconnection structure **106**. In additionally, a portion of each of the solder pillars **116** is protruded from the top surface of the molding layer **112**, and is higher than the surface **202a** of the chip **210**, so that, the input/output terminals may be conveniently arranged around the semiconductor package **300** in the subsequent process.

[0039] People well-skilled in the art should fully understand that the semiconductor package, the semiconductor bonding structure and/or the fabricating method thereof are not limited to be what is shown in the aforementioned embodiments, and which may further include other examples based on practical product requirements. The following description will detail other different embodiments or variant embodiments of the semiconductor package, the semiconductor bonding structure and/or the fabricating method thereof in the present disclosure. To simplify the description, the following description will detail the dissimilarities among the different embodiments and the identical features will not be redundantly described. In order to compare the differences between the embodiments easily, the identical components in each of the following embodiments are marked with identical symbols.

[0040] Please refer to FIG. **7** to FIG. **8**, which illustrate schematic diagrams of a fabricating method of a semiconductor bonding structure and a semiconductor package according to the second embodiment of the present disclosure. The formal steps in the present embodiment are substantially the same as those in the aforementioned embodiment, as shown in FIG. **1** to FIG. **4**, and which may not be redundantly described herein. The difference between the present embodiment and the aforementioned embodiment is in that, a conductive structure of the present embodiment includes at least one redistribution layer (RDL) **122** and at least one solder ball **126**.

[0041] Precisely speaking, as shown in FIG. **7**, the redistribution layer **122** is formed on the molding layer **112**, and the formation of the redistribution layer **122** includes but not limited to the following steps. Firstly, an electroplating process is performed to form a redistribution material layer (not shown in the drawings), with the redistribution material layer conformally covering on the surfaces of the molding layer **112** and the openings **114** as shown in FIG. **4**, over the upper surface **106a**. Then, the redistribution material layer is partially removed through a patterning process, to form a plurality of recesses **124** to expose the molding layer **112** underneath, and the redistribution layers **122** are formed at the same time. In this way, the redistribution layers **122** may be electrically connected to the bonding pads **108** within the interconnection structure **106**, and to lead out the signals of the bonding pads **108** to the surface **202a** of each chip **210**, so as to serve as a path for electrically connecting the bonding pads **108** with other signals. Then, the solder balls **126** are correspondingly formed on the redistribution layers **122**, with each of the solder balls **126** being located over the surface **202a** of each chip **210**. It is noted that, although the present embodiment is only exemplified by sequentially arranging the solder balls **126** over each chip **210**, people well-skilled in the art should fully realized that the practical locations and the number of the

solder balls **126** and the redistribution layers **122** may both be adjusted according to the practical arranging requirements of the input/output terminals in a device. For example, in one embodiment, if being viewed through a top view (not shown in the drawings), the disposing locations of the solder balls **126** may be arranged in an array arrangement (not shown in the drawings) or a matrix arrangement (not shown in the drawings), which is beneficial on arranging a relatively large number of the input/output terminals, but is not limited thereto.

[0042] After that, the primary substrate **100** and the plurality of the interconnection structures **106** of the semiconductor structure are cut into a plurality of chips **130** as shown in FIG. **8** through a plurality of scribe lines **128** located at the junctions of the die regions in the primary substrate **100** respectively, in the subsequent die saw process. It is noted that, each of the chips **130** includes a substrate **100a** and the interconnection structure **106** disposed on the surface **104** of the substrate **100a**. Meanwhile, a plurality of semiconductor packages **302** as shown in FIG. **8** is formed thereby. Through the aforementioned processes, the fabricating method of the semiconductor bonding structure and the semiconductor package of the second embodiment in the present disclosure is accomplished, wherein the semiconductor package **302** may be further mounted to a circuit board (not shown in the drawings) or other secondary packaging substrates to form the required integrated circuits. Alternatively, the semiconductor package **302** may also be used directly as a wafer-level CSP.

[0043] As shown in FIG. **8**, the semiconductor package **302** obtained by the fabricating method of the present embodiment includes the chip **130**, the chip **210** stacked on the chip **130**, and the conductive structure (for example including the redistribution layer **122** and the solder ball **126**), wherein the chip **130** and the chip **210** are connected with each other via a similar manner as that of the semiconductor package **300** in the first embodiment, and which will not be redundant described herein after. In particular, the redistribution layers **122** and the solder balls **126** disposed over the upper surfaces **106a** of the interconnection structure **106** on the chip **120** is configured as the conductive structure of the present embodiment, and the redistribution layers **122** directly covers the surfaces of the openings **114** as shown in FIG. **4**, so as to directly contact the covering layer **110** disposed at the bottom of each opening **114** and further extend to the top surface of the molding layer **112**. In this way, the solder balls **126** may be disposed on the surface **202a** of the chip **210**, and is higher than the top surface of the molding layer **112**, to dramatically increase the disposing locations of the input/output terminals.

[0044] Please refer to FIG. **9** to FIG. **11**, which illustrate schematic diagrams of a fabricating method of a semiconductor bonding structure and a semiconductor package according to the third embodiment of the present disclosure. The formal steps in the present embodiment are substantially the same as those in the aforementioned second embodiment, and all the similarities will not be redundantly described herein. The difference between the present embodiment and the aforementioned embodiment is in that, a protection layer **134** is additionally formed on the redistribution layers **122**, to protect the redistribution layers **122**.

[0045] Precisely speaking, as shown in FIG. **9**, a protection material layer **132** is formed conformally to cover the redistribution layers **122** and the molding layer **112**, wherein the protection material layer **132** further fills in the openings **114** as shown in FIG. **4**. The protection material layer **132** for example includes a material like polyimide (PI), polyethylene (PVO), or other materials suitable serving as a passivation layer, but is not limited thereto.

[0046] As shown in FIG. **10**, the protection material layer **132** is partially removed through performing a patterning process, to expose the redistribution layers **122** underneath, and to form the protection layer **134** at the same time. After that, a plurality of solder balls **136** are formed on the exposed redistribution layers **122**. In this way, the solder balls **136** may also be disposed over the surface **202a** of each chip **210**, and a portion of the protection layer **134a** may be sandwiched between each of the solder balls **136** and the redistribution layers **122**. After that, the primary substrate **100** and the plurality of the interconnection structures **106** of the semiconductor structure

are cut into a plurality of chips **140** as shown in FIG. **11** through a plurality of scribe lines **138** located at the junctions of the die regions of the primary substrate **100** respectively, in the subsequent die saw process. It is noted that, each of the chips **140** includes a substrate **100a** and the interconnection structure **106** disposed on the surface **104** of the substrate **100a**. Meanwhile, a plurality of semiconductor packages **304** as shown in FIG. **11** are formed thereby.

[0047] Through the aforementioned processes, the fabricating method of the semiconductor bonding structure and the semiconductor package of the third embodiment in the present disclosure is accomplished, wherein the semiconductor package **304** may be further mounted to a circuit board (not shown in the drawings) or other secondary packaging substrates via the solder balls **136** to form the required integrated circuits. Alternatively, the semiconductor package **304** may also be used directly as a wafer-level CSP.

[0048] As shown in FIG. **11**, the semiconductor package **304** obtained by the fabricating method of the present embodiment includes the chip **140**, the chip **210** stacked on the chip **140**, and the conductive structure (for example including the redistribution layer **122** and the solder ball **136**), wherein the chip **140** and the chip **210** are connected with each other via a similar manner as that of the semiconductor packages **300**, **302** in the aforementioned embodiments, and which will not be redundant described herein after. It is noted that, the protection layer **134** is additionally disposed between the redistribution layers **122** and the solder balls **136**, to protect the redistribution layers **122** underneath.

[0049] Please refer to FIG. **12**, which illustrates a schematic diagram of a fabricating method of a semiconductor bonding structure and a semiconductor package according to the fourth embodiment of the present disclosure. The formal steps in the present embodiment are substantially the same as those in the aforementioned embodiment, and which may not be redundantly described herein. The difference between the present embodiment and the aforementioned embodiment is in that, the covering layer **110** of the present embodiment includes a non-conductive material having protection capability, such as a dielectric material.

[0050] Accordingly, while forming the openings **144** through the photolithography and etching process, the dry etching process or the laser burning process, the openings **144** have to further penetrate the covering layer **110** at the bottom, to expose the bonding pads **108** underneath. In one embodiment, the covering layer **110** may be removed completely. Alternately, the covering layer **110** may also be partially removed till exposing the bonding pads **108**, with a portion of the covering layer **110a** being remained at the bottom of the openings **144**, as shown in FIG. **12**. Then, the conductive structure formed subsequently, for example the solder pillars **116** formed in the aforementioned first embodiment or the redistribution layers **122** formed in the aforementioned second embodiment, will directly contact the bonding pads **108** underneath to electrically connect to the interconnection structure **106**. With these arrangements, the semiconductor package (not shown in the drawings) obtained by the fabricating method of the present embodiment also includes the conductive structure disposed on the upper surfaces **106a** of the interconnection structure **106**, with the conductive structure being disposed at one side of the chip **210**, and partially protruded from the top surface of the molding layer **112**, thereby beneficial on arranging the input/output terminals.

[0051] Overall speaking, the fabricating method of the present disclosure forms the semiconductor package by using copper-to-copper direct bonding in a chip-to-wafer bonding manner, so that, the fabricating complexity and cost of the TSV may be omitted, thereby improving the stress interference caused by the TSV structure and saving the process window for the TSV. Therefore, the present disclose is allowable to form the semiconductor package with more reliable structure under a simplified fabricating process. In addition, the semiconductor package obtained by the fabricating method of the present disclosure includes a chip disposed on an upper surface of an interconnection structure within a wafer-level semiconductor structure, and a conductive structure disposed on another upper surface of the interconnection structure, with the conductive structure

being disposed at a location higher than the top surface of the chip, for conveniently arranging the input/output terminals thereon in the subsequent processes. The conductive structure of the present disclosure for example includes a redistribution layer, a solder ball and/or a solder pillar, but not limited thereto. Accordingly, the semiconductor package of the present disclosure may be used directly as a CSP of wafer-level package, being beneficial on thin and short packaging application, or be further mounted to a circuit board or other secondary packaging substrates, thereby forming the required integrated circuits.

[0052] Those skilled in the art will readily observe that numerous modifications and alterations of the device and method may be made while retaining the teachings of the invention. Accordingly, the above disclosure should be construed as limited only by the metes and bounds of the appended claims.

Claims

1. A semiconductor bonding structure, comprising: a primary substrate; a plurality of first interconnection structures, disposed on the primary substrate, wherein an upper surface of each of the first interconnection structures comprises a first upper surface and a second upper surface; a plurality of chips, disposed on the first interconnection structures and electrically connected to the first interconnection structures respectively, each of the chips comprising: a substrate; and a second interconnection structure disposed on the substrate, wherein the second interconnection structure directly and electrically connects to the first upper surface of each of the first interconnection structures; and a plurality of conductive structures, disposed at one side of each of the chips, and disposed on the second upper surface of each of the first interconnection structures, the conductive structures electrically connected to the first interconnection structures respectively.
 2. The semiconductor bonding structure according to claim 1, wherein each of the conductive structures comprises at least one solder pillar, and a portion of the solder pillar is protruded from the second upper surface of each of the first interconnection structure.
 3. The semiconductor bonding structure according to claim 1, wherein each of the conductive structures further comprising: at least one redistribution layer directly disposed on the second upper surface of each of the first interconnection structures; and at least one solder ball disposed on the at least one redistribution layer, over a surface of each of the chips.
 4. The semiconductor bonding structure according to claim 3, wherein the conductive structures further comprising: a protection layer, covered on the at least one redistribution layer, and a portion of the protection layer being sandwiched between the at least one redistribution layer and the at least one solder ball.
 5. The semiconductor bonding structure according to claim 1, further comprises: a plurality of bonding pads embedded in each of the first interconnection structures and electrically connected to the conductive structures respectively.
 6. The semiconductor bonding structure according to claim 1, further comprising: a molding layer, covered on the chips and the first interconnection structures, wherein each of the conductive structures is partially disposed in the molding layer.
-