

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280563

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

Chen; Chang-Yih et al.

EMBEDDED HIGH-VOLTAGE SEMICONDUCTOR DEVICE AND FABRICATION METHOD THEREOF

Abstract

An embedded high-voltage semiconductor device includes a substrate with a low-voltage device region and a high-voltage device region; an ILD layer located on the substrate; a first interconnection metal layer located on the ILD layer in the low-voltage device region a; a first IMD layer between the ILD layer and the first interconnection metal layer; a second interconnection metal layer located on the ILD layer in the high-voltage device region; and a second IMD layer between the ILD layer and the second interconnection metal layer. The second IMD layer is denser than the first IMD layer.

Inventors: Chen; Chang-Yih (Tainan City, TW), Lee; Kuo-Hsing (Hsinchu County, TW), Lin; Hung-Chan (Tainan City, TW), Lin; Chun-Hsien (Tainan City, TW), Tsai; Chih-Chin (Tainan City, TW), Chen; Yi-Hsiu (Pingtung County, TW), Chen; Hsin-Hsien (New Taipei City, TW)

Applicant: UNITED MICROELECTRONICS CORP. (Hsin-Chu City, TW)

Family ID: 96880773

Assignee: UNITED MICROELECTRONICS CORP. (Hsin-Chu City, TW)

Appl. No.: 18/631088

Filed: April 10, 2024

Foreign Application Priority Data

TW

113107636

Mar. 04, 2024

Publication Classification

Int. Cl.: H01L29/78 (20060101); H01L21/762 (20060101); H01L21/768 (20060101);
H01L29/66 (20060101)

Background/Summary

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] The invention relates to the field of semiconductor technology, particularly to an embedded high-voltage (eHV) semiconductor device and its manufacturing method.

2. Description of the Prior Art

[0002] To reduce the RC delay, there has been a desire to replace the dielectrics in metal interconnect structures with materials having lower dielectric constants. Such materials are referred to as low-k and ultra-low-k dielectrics. A low-k dielectric is a material having a smaller dielectric constant than SiO₂. SiO₂ has a dielectric constant of about 4.0. An ultra-low-k dielectric is a material having a dielectric constant of about 2.1 or less.

[0003] Due to the reduction in the thickness of the low-k or ultra-low-k inter-metal dielectric layer between the M1 metal and the M0 metal, the medium-voltage or high-voltage area of the embedded high-voltage device (eHV device) may fail to pass 8V TDDB (Time-Dependent Dielectric Breakdown) reliability test. Therefore, this technical field still needs an improved embedded high-voltage semiconductor device and its manufacturing method to solve the problem of inter-metal dielectric layer breakdown.

SUMMARY OF THE INVENTION

[0004] It is one object of the present invention to provide an improved embedded high-voltage semiconductor device and its manufacturing method to solve the shortcomings or deficiencies of the existing technology.

[0005] One aspect of the invention provides an embedded high-voltage (eHV) semiconductor device including a substrate having a low-voltage device region and a high-voltage device region thereon; an inter-layer dielectric (ILD) layer on the substrate; a first trench isolation region in the substrate within the low-voltage device region; a first gate in the ILD layer and on the first trench isolation region; a first gate contact in the ILD layer and on the first gate; a first interconnection metal layer overlying the first gate contact; a first inter-metal dielectric (IMD) layer on the ILD layer and between the first interconnection metal layer and the first gate contact; a second trench isolation region in the substrate within the high-voltage device region; a second gate in the ILD layer and on the second trench isolation region; a second gate contact in the ILD layer and on the second gate; a second interconnection metal layer overlying the second gate contact; and a second inter-metal dielectric (IMD) layer on the ILD layer and between the second interconnection metal layer and the second gate contact. The second IMD layer is denser than the first IMD layer.

[0006] According to some embodiments, the second interconnection metal layer overlaps the second gate contact.

[0007] According to some embodiments, the first IMD layer comprises an ultra-low dielectric constant material layer.

[0008] According to some embodiments, the second IMD layer comprises a TEOS-based oxide layer or a high-density plasma (HDP) oxide layer.

[0009] According to some embodiments, the second interconnection metal layer is disposed in the second IMD layer.

[0010] According to some embodiments, the first IMD layer extends onto a top surface of the

second IMD layer.

[0011] According to some embodiments, the second interconnection metal layer is disposed in the first IMD layer that extends onto the top surface of the second IMD layer.

[0012] According to some embodiments, the first gate contact and the second gate contact comprise tungsten.

[0013] According to some embodiments, the first gate and the second gate are metal gates.

[0014] According to some embodiments, the first IMD layer and the second IMD layer are ultra-low dielectric constant material layer.

[0015] Another aspect of the invention provides a method for forming an embedded high-voltage (eHV) semiconductor device. A substrate having a low-voltage device region and a high-voltage device region thereon is provided. An inter-layer dielectric (ILD) layer is formed on the substrate. A first trench isolation region is formed in the substrate within the low-voltage device region. A first gate is disposed in the ILD layer and on the first trench isolation region. A first gate contact is formed in the ILD layer and on the first gate. A first interconnection metal layer is formed on the first gate contact. A first inter-metal dielectric (IMD) layer is formed on the ILD layer and between the first interconnection metal layer and the first gate contact. A second trench isolation region is formed in the substrate within the high-voltage device region. A second gate is formed in the ILD layer and on the second trench isolation region. A second gate contact is formed in the ILD layer and on the second gate. A second interconnection metal layer is formed on the second gate contact. A second inter-metal dielectric (IMD) layer is formed on the ILD layer and between the second interconnection metal layer and the second gate contact. The second IMD layer is denser than the first IMD layer.

[0016] According to some embodiments, the second interconnection metal layer overlaps the second gate contact.

[0017] According to some embodiments, the first IMD layer comprises an ultra-low dielectric constant material layer.

[0018] According to some embodiments, the second IMD layer comprises a TEOS-based oxide layer or a high-density plasma (HDP) oxide layer.

[0019] According to some embodiments, the second interconnection metal layer is disposed in the second IMD layer.

[0020] According to some embodiments, the first IMD layer extends onto a top surface of the second IMD layer.

[0021] According to some embodiments, the second interconnection metal layer is disposed in the first IMD layer that extends onto the top surface of the second IMD layer.

[0022] According to some embodiments, the first gate contact and the second gate contact comprise tungsten.

[0023] According to some embodiments, the first gate and the second gate are metal gates.

[0024] According to some embodiments, the first IMD layer and the second IMD layer are ultra-low dielectric constant material layer.

[0025] These and other objectives of the present invention will no doubt become obvious to those of ordinary skill in the art after reading the following detailed description of the preferred embodiment that is illustrated in the various figures and drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0026] FIGS. 1-7 illustrate a method of forming an embedded high-voltage (eHV) semiconductor device according to an embodiment of the present invention.

[0027] FIGS. 8-14 illustrate a method of forming an eHV semiconductor device according to

another embodiment of the present invention.

[0028] FIGS. **15-18** illustrate a method of forming an eHV semiconductor device according to still another embodiment of the present invention.

DETAILED DESCRIPTION

[0029] In the following detailed description of the disclosure, reference is made to the accompanying drawings, which form a part hereof, and in which is shown, by way of illustration, specific embodiments in which the invention may be practiced. These embodiments are described in sufficient detail to enable those skilled in the art to practice the invention.

[0030] Other embodiments may be utilized, and structural, logical, and electrical changes may be made without departing from the scope of the present invention. Therefore, the following detailed description is not to be considered as limiting, but the embodiments included herein are defined by the scope of the accompanying claims.

[0031] Please refer to FIGS. **1** to **7**, which illustrate a method of forming an embedded high-voltage (eHV) semiconductor device **1** according to an embodiment of the present invention. For example, the eHV semiconductor device **1** of the present invention can be applied to a display driver integrated circuit (DDIC) using fin field effect transistor (FinFET) processes at 17 nm node or beyond.

[0032] As shown in FIG. **1**, a substrate **100** is first provided, for example, a silicon substrate, but is not limited thereto. According to an embodiment of the present invention, the substrate **100** has a low-voltage device region RL and a high-voltage device region RH. A trench isolation region SI1 and a trench isolation region SI2 are respectively formed in the substrate **100** in the low-voltage device region RL and the high-voltage device region RH. The trench isolation region SI1 and the trench isolation region SI2 can be formed using a shallow trench isolation (STI) process.

[0033] According to an embodiment of the present invention, in the low-voltage device region RL, a circuit element **20** is formed on the substrate **100** adjacent to the trench isolation region SI1. In the high-voltage device region RH, a circuit element **30** is formed on the substrate **100** adjacent to the trench isolation region SI2. According to an embodiment of the present invention, for example, the circuit element **20** may be a fin field effect transistor (FinFET) device, but is not limited thereto. According to an embodiment of the present invention, the operating voltage of the circuit element **20** may be less than 5V, for example, 1.8V. The circuit element **20** may include a fin structure **201** and a metal gate **202** extending across the fin structure **201**. According to an embodiment of the present invention, for example, the circuit element **30** may be a high-voltage transistor element with operating voltages greater than 5V. For example, the circuit element **20** may be a planar field effect transistor including a drain or source doped region **301** and a gate **302**.

[0034] According to an embodiment of the present invention, a gate **204** and a gate **304** are formed on the trench isolation region SI1 and the trench isolation region SI2 respectively. According to an embodiment of the present invention, for example, the gate **204** and the gate **304** may be metal gates, but are not limited thereto.

[0035] Subsequently, a chemical vapor deposition (CVD) process may be performed to deposit an interlayer dielectric (ILD) layer **410** on the substrate **100** in a blanket manner. A metallization process is then performed to form a diffusion contact MD1 and a gate contact MP1 in the ILD layer **410** in the low-voltage device region RL, and a diffusion contact MD2 and a gate contact MP2 in the ILD layer **410** in the high-voltage device region RH. According to an embodiment of the present invention, the diffusion contact MD1 directly contacts the doped region on the fin structure **201**, the gate contact MP1 directly contacts the gate **204**, the diffusion contact MD2 directly contacts the drain or source doped region **301**, and the gate contact MP2 directly contacts the gate **304**. According to an embodiment of the present invention, the gate **204** and the gate contact MP1 are located directly above the trench isolation region SI1, and the gate **304** and the gate contact MP2 are located directly above the trench isolation region SI2. According to an embodiment of the present invention, the gate contact MP1 and the gate contact MP2 may contain tungsten, but are not

limited thereto.

[0036] A chemical vapor deposition process is then performed to deposit an inter-metal dielectric (IMD) layer **420** on the substrate **100** in a blanket manner. According to an embodiment of the present invention, for example, the IMD layer **420** may include a structurally denser dielectric layer such as a TEOS oxide layer or a high-density plasma (HDP) oxide layer.

[0037] As shown in FIG. **2**, subsequently, a metallization process, such as a damascene copper process, is performed to form an interconnection metal layer **431** and a via **432** in the IMD layer **420** in the high-voltage device region RH. The via **432** electrically connects the interconnection metal layer **431** to the underlying diffusion contact MD2. According to an embodiment of the present invention, the interconnection metal layer **431** extends laterally into the region directly above the gate **304** and the gate contact MP2. Therefore, when viewed from above, the interconnection metal layer **431** overlaps the gate contact MP2. Between the interconnection metal layer **431** and gate contact MP2 is the IMD layer **420**.

[0038] As shown in FIG. **3**, a photolithography process is then performed to form a photoresist pattern PR on the high-voltage device region RH. At this point, the photoresist pattern PR covers the high-voltage device region RH, while exposes the IMD layer **420** of the low-voltage device region RL.

[0039] As shown in FIG. **4**, an etching process, for example, an anisotropic dry etching process is then performed, using the photoresist pattern PR as an etching mask to remove the IMD layer **420** in the low-voltage device region RL that is not covered by the photoresist pattern PR, thereby exposing the ILD layer **410**, the diffusion contact MD1 and the gate contact MP1 in the low-voltage device region RL.

[0040] As shown in FIG. **5**, a chemical vapor deposition process is then performed to deposit an inter-metal dielectric (IMD) layer **440** on the substrate **100** in a blanket manner. According to an embodiment of the present invention, for example, the IMD layer **440** may include low dielectric constant (low k) and ultra-low dielectric constant (ultra-low k) dielectric materials. For example, the IMD layer **440** may include porous silicon dioxide, porous carbon-doped silicon dioxide, porous SiLK, porous SiCOH layers, or the like. According to an embodiment of the present invention, the IMD layer **420** is denser than the IMD layer **440**.

[0041] As shown in FIG. **6**, a chemical mechanical polishing (CMP) process is then performed to polish the surface of the IMD layer **440** so that the surface of the IMD layer **440** in the low-voltage device region RL is coplanar with the surface of the IMD layer **440** in the high-voltage device region RH.

[0042] As shown in FIG. **7**, a metallization process, such as a damascene copper process, is then performed to form an interconnection metal layer **451** and a via **452** in the IMD layer **440** in the low-voltage device region RL. The via **452** electrically connect the metal layer **451** to the underlying diffusion contact MD1. According to an embodiment of the present invention, the interconnection metal layer **451** extends laterally to the region directly above the gate **204** and the gate contact MP1, so when viewed from above, the interconnection metal layer **451** overlaps the gate contact MP1. Between the interconnection metal layer **451** and the gate contact MP1 is the IMD layer **440**. A CMP process can be continued to expose the interconnection metal layer **431** and the interconnection metal layer **451**, and then the subsequent metal interconnection process can be performed.

[0043] Please refer to FIGS. **8** to **14**, which illustrate a method of forming an eHV semiconductor device **2** according to another embodiment of the present invention, wherein like regions, layers or elements are designated by like numeral numbers or labels. For example, the eHV semiconductor device **2** of the present invention can be applied to a display driver integrated circuit (DDIC) using a FinFET process at 17 nm node or beyond.

[0044] As shown in FIG. **8**, a substrate **100** is first provided, for example, a silicon substrate, but is not limited thereto. According to an embodiment of the present invention, the substrate **100** has a

low-voltage device region RL and a high-voltage device region RH. A trench isolation region SI1 and a trench isolation region SI2 are respectively formed in the substrate **100** in the low-voltage device region RL and the high-voltage device region RH. The trench isolation region SI1 and the trench isolation region SI2 can be formed using a shallow trench insulation (STI) process.

[0045] According to an embodiment of the present invention, in the low-voltage device region RL, a circuit element **20** is formed on the substrate **100** adjacent to the trench isolation region SI1. In the high-voltage device region RH, a circuit element **30** is formed on the substrate **100** adjacent to the trench isolation region SI2. According to an embodiment of the present invention, for example, the circuit element **20** may be a FinFET device, but is not limited thereto. According to an embodiment of the present invention, the operating voltage of the circuit element **20** may be less than 5V, for example, 1.8V. The circuit element **20** may include a fin structure **201** and a metal gate **202** extending across the fin structure **201**. According to an embodiment of the present invention, for example, the circuit element **30** may be a high-voltage transistor device with operating voltages greater than 5V. For example, the circuit element **20** may be a planar field effect transistor including a drain or source doped region **301** and a gate **302**.

[0046] According to an embodiment of the present invention, a gate **204** and a gate **304** are formed on the trench isolation region SI1 and the trench isolation region SI2, respectively. According to an embodiment of the present invention, for example, the gate **204** and the gate **304** may be metal gates, but are not limited thereto.

[0047] Subsequently, a chemical vapor deposition process may be performed to deposit an interlayer dielectric (ILD) layer **410** on the substrate **100** in a blanket manner. A metallization process is then performed to form a diffusion contact MD1 and a gate contact MP1 in the ILD layer **410** in the low-voltage device region RL, and a diffusion contact MD2 and a gate contact MP2 in the ILD layer in the high-voltage device region RH. According to an embodiment of the present invention, the diffusion contact MD1 directly contacts the doped region on the fin structure **201**, the gate contact MP1 directly contacts the gate **204**, the diffusion contact MD2 directly contacts the drain or source doped region **301**, and the gate contact MP2 directly contacts gate **304**. According to an embodiment of the present invention, the gate **204** and the gate contact MP1 are located directly above the trench isolation region SI1, and the gate **304** and the gate contact MP2 are located directly above the trench isolation region SI2. According to an embodiment of the present invention, the gate contact MP1 and the gate contact MP2 may contain tungsten, but are not limited thereto.

[0048] A chemical vapor deposition process is then performed to deposit an inter-metal dielectric (IMD) layer **420** on the substrate **100** in a blanket manner. According to an embodiment of the present invention, for example, the IMD layer **420** may include a structurally denser dielectric layer such as a TEOS oxide layer or a high-density plasma (HDP) oxide layer.

[0049] As shown in FIG. 9, a metallization process, such as a damascene copper process, is then performed to form a via **432** in the IMD layer **420** in the high-voltage device region RH. The via **432** is electrically connected with the underlying diffusion contact MD2.

[0050] As shown in FIG. 10, a photolithography process is then performed to form a photoresist pattern PR on the high-voltage device region RH. The photoresist pattern PR covers the high-voltage device region RH, while exposes the IMD layer **420** in the low-voltage device region RL.

[0051] As shown in FIG. 11, an etching process, for example, an anisotropic dry etching process is then performed, using the photoresist pattern PR as an etching mask to remove the IMD layer **420** in the low-voltage device region RL that is not covered by the photoresist pattern PR, thereby exposing the ILD layer **410**, the diffusion contact MD1 and the gate contact MP1 in the low-voltage device region RL.

[0052] As shown in FIG. 12, a chemical vapor deposition process is then performed to deposit an inter-metal dielectric (IMD) layer **440** on the substrate **100** in a blanket manner. According to an embodiment of the present invention, for example, the IMD layer **440** may include low-k and ultra-

low-k dielectric materials. For example, IMD layer **440** may include porous silicon dioxide, porous carbon-doped silicon dioxide, porous SiLK, porous SiCOH layers, or the like. According to an embodiment of the present invention, the IMD layer **420** is denser than the IMD layer **440**.

[0053] As shown in FIG. **13**, a chemical mechanical polishing (CMP) process is then performed to polish the surface of the IMD layer **440** so that the surface of the IMD layer **440** in the low-voltage device region RL is coplanar with the surface of the IMD layer **440** in the high-voltage device region RH. According to an embodiment of the present invention, in the high-voltage device region RH, the IMD layer **440** extends to the top surface of the IMD layer **420**.

[0054] As shown in FIG. **14**, a metallization process, such as a damascene copper process, is performed to form an interconnection metal layer **431** in the IMD layer **440** in the high-voltage device region RH, and an interconnection metal layer **431** in the IMD layer **440** in the low-voltage device region RL. The interconnection metal layer **431** is electrically connected to the via **432**, and the via **452** electrically connects the interconnection metal layer **451** to the underlying diffusion contact MD1. According to an embodiment of the present invention, an interconnection metal layer **431** is disposed in the IMD layer **440** that extends to the top surface of the IMD layer **420**.

[0055] According to an embodiment of the present invention, the interconnection metal layer **431** extends laterally to the region directly above the gate **304** and the gate contact MP2. When viewed from above, the interconnection metal layer **431** overlaps the gate contact MP2. Between the interconnection metal layer **431** and the gate contact MP2 is the IMD layer **420**. According to an embodiment of the present invention, the interconnection metal layer **451** extends laterally to the region directly above the gate **204** and the gate contact MP1. When viewed from above, the interconnection metal layer **451** overlaps the gate contact MP1. Between the interconnection metal layer **451** and the gate contact MP1 is the IMD layer **440**.

[0056] Please refer to FIGS. **15** to **18**, which illustrate a method of forming an eHV semiconductor device **3** according to still another embodiment of the present invention, wherein like regions, layers or elements are designated by like numeral numbers or labels. For example, the eHV semiconductor device **3** of the present invention can be applied to a display driver integrated circuit (DDIC) using a FinFET process at 17 nm node or beyond.

[0057] As shown in FIG. **15**, a substrate **100** is provided, for example, a silicon substrate, but is not limited thereto. According to an embodiment of the present invention, the substrate **100** has a low-voltage device region RL and a high-voltage device region RH. A trench isolation region SI1 and a trench isolation region SI2 are respectively formed in the substrate **100** in the low-voltage device region RL and the high-voltage device region RH. The trench isolation region SI1 and the trench isolation region SI2 can be formed using a shallow trench insulation (STI) process.

[0058] According to an embodiment of the present invention, in the low-voltage device region RL, a circuit element **20** is formed on the substrate **100** adjacent to the trench isolation region SI1. In the high-voltage device region RH, a circuit element **30** is formed on the substrate **100** adjacent to the trench isolation region SI2. According to an embodiment of the present invention, for example, the circuit element **20** may be a FinFET device, but is not limited thereto. According to an embodiment of the present invention, the operating voltage of the circuit element **20** may be less than 5V, for example, 1.8V. The circuit element **20** may include a fin structure **201** and a metal gate **202** extending across the fin structure **201**. According to an embodiment of the present invention, for example, the circuit element **30** may be a high-voltage transistor element with operating voltages greater than 5V. For example, the circuit element **20** may be a planar field effect transistor including a drain or source doped region **301** and a gate **302**.

[0059] According to an embodiment of the present invention, a gate **204** and a gate **304** are formed on the trench isolation region SI1 and the trench isolation region SI2, respectively. According to an embodiment of the present invention, for example, the gate **204** and the gate **304** may be metal gates, but are not limited thereto.

[0060] Subsequently, a chemical vapor deposition process may be performed to deposit an

interlayer dielectric (ILD) layer **410** on the substrate **100** in a blanket manner. A metallization process is then performed to form a diffusion contact MD**1** and a gate contact MP**1** in the ILD layer **410** in the low-voltage device region RL, and a diffusion contact MD**2** and a gate contact MP**2** in the ILD layer in the high-voltage device region RH. According to an embodiment of the present invention, the diffusion contact MD**1** directly contacts the doped region on the fin structure **201**, the gate contact MP**1** directly contacts the gate **204**, the diffusion contact MD**2** directly contacts the drain or source doped region **301**, and the gate contact MP**2** directly contacts the gate **304**. According to an embodiment of the present invention, the gate **204** and the gate contact MP**1** are located directly above the trench isolation region SI**1**, and the gate **304** and the gate contact MP**2** are located directly above the trench isolation region SI**2**. According to an embodiment of the present invention, the gate contact MP**1** and the gate contact MP**2** may contain tungsten, but are not limited thereto.

[0061] Subsequently, a chemical vapor deposition process may be performed to deposit an inter-metal dielectric (IMD) layer **440** on the substrate **100** in a blanket manner. According to an embodiment of the present invention, for example, the IMD layer **440** may include UV-curable low-k or ultra-low-k dielectric materials. For example, the IMD layer **440** may include porous silicon dioxide, porous carbon-doped silicon dioxide, porous SiLK, porous SiCOH layers, or the like. A mask layer **510** is formed on the IMD layer **440** in the low-voltage device region RL. For example, the mask layer **510** may include silicon oxynitride, but is not limited thereto. At this point, the IMD layer **440** in the high-voltage device region RH is not covered by the mask layer **510**, and is exposed.

[0062] As shown in FIG. **16**, a UV curing process is performed so that the IMD layer **440** in the high-voltage device region RH is directly irradiated with ultraviolet light to form a densified IMD layer **440d**. According to an embodiment of the present invention, the IMD layer **440** and the IMD layer **440d** are both ultra-low dielectric constant material layers. According to an embodiment of the present invention, for example, the IMD layer **440** in the high-voltage device region RH is irradiated with ultraviolet light for about 300 seconds, which may increase the hardness of the IMD layer **440** in the high-voltage device region RH from about 0.75 GPa to about 1-2 GPa, thereby forming the densified IMD layer **440d**.

[0063] As shown in FIG. **17**, after the UV curing process is completed, an etching process, such as a wet etching process, is performed to remove the mask layer **510** so as to expose the IMD layer **440** in the low-voltage device region RL.

[0064] As shown in FIG. **18**, a metallization process, such as a damascene copper process is then performed, to form an interconnection metal layer **431** and a via **432** in the IMD layer **440d** in the high-voltage device region RH, and an interconnection metal layer **451** and a via **452** in the IMD **440** in the low-voltage device region RL.

[0065] According to an embodiment of the present invention, the interconnection metal layer **431** extends laterally to the region directly above the gate **304** and the gate contact MP**2**. When viewed from above, the interconnection metal layer **431** overlaps the gate contact MP**2**. Between the interconnection metal layer **431** and the gate contact MP**2** is the IMD layer **440d**. According to an embodiment of the present invention, the interconnection metal layer **451** extends laterally to the region directly above the gate **204** and the gate contact MP**1**. When viewed from above, the interconnection metal layer **451** overlaps the gate contact MP**1**. Between the interconnection metal layer **451** and the gate contact MP**1** is the IMD layer **440**.

[0066] Those skilled in the art will readily observe that numerous modifications and alterations of the device and method may be made while retaining the teachings of the invention. Accordingly, the above disclosure should be construed as limited only by the metes and bounds of the appended claims.

Claims

1. An embedded high-voltage (eHV) semiconductor device, comprising: a substrate having a low-voltage device region and a high-voltage device region thereon; an inter-layer dielectric (ILD) layer on the substrate; a first trench isolation region in the substrate within the low-voltage device region; a first gate in the ILD layer and on the first trench isolation region; a first gate contact in the ILD layer and on the first gate; a first interconnection metal layer overlying the first gate contact; a first inter-metal dielectric (IMD) layer on the ILD layer and between the first interconnection metal layer and the first gate contact; a second trench isolation region in the substrate within the high-voltage device region; a second gate in the ILD layer and on the second trench isolation region; a second gate contact in the ILD layer and on the second gate; a second interconnection metal layer overlying the second gate contact; and a second inter-metal dielectric (IMD) layer on the ILD layer and between the second interconnection metal layer and the second gate contact, wherein the second IMD layer is denser than the first IMD layer.
2. The eHV semiconductor device according to claim 1, wherein the second interconnection metal layer overlaps the second gate contact.
3. The eHV semiconductor device according to claim 1, wherein the first IMD layer comprises an ultra-low dielectric constant material layer.
4. The eHV semiconductor device according to claim 3, wherein the second IMD layer comprises a TEOS-based oxide layer or a high-density plasma (HDP) oxide layer.
5. The eHV semiconductor device according to claim 4, wherein the second interconnection metal layer is disposed in the second IMD layer.
6. The eHV semiconductor device according to claim 4, wherein the first IMD layer extends onto a top surface of the second IMD layer.
7. The eHV semiconductor device according to claim 6, wherein the second interconnection metal layer is disposed in the first IMD layer that extends onto the top surface of the second IMD layer.
8. The eHV semiconductor device according to claim 1, wherein the first gate contact and the second gate contact comprise tungsten.
9. The eHV semiconductor device according to claim 1, wherein the first gate and the second gate are metal gates.
10. The eHV semiconductor device according to claim 1, wherein the first IMD layer and the second IMD layer are ultra-low dielectric constant material layer.
11. A method for forming an embedded high-voltage (eHV) semiconductor device, comprising: providing a substrate having a low-voltage device region and a high-voltage device region thereon; forming an inter-layer dielectric (ILD) layer on the substrate; forming a first trench isolation region in the substrate within the low-voltage device region; forming a first gate disposed in the ILD layer and on the first trench isolation region; forming a first gate contact in the ILD layer and on the first gate; forming a first interconnection metal layer overlying the first gate contact; forming a first inter-metal dielectric (IMD) layer on the ILD layer and between the first interconnection metal layer and the first gate contact; forming a second trench isolation region in the substrate within the high-voltage device region; forming a second gate in the ILD layer and on the second trench isolation region; forming a second gate contact in the ILD layer and on the second gate; forming a second interconnection metal layer overlying the second gate contact; and forming a second inter-metal dielectric (IMD) layer on the ILD layer and between the second interconnection metal layer and the second gate contact, wherein the second IMD layer is denser than the first IMD layer.
12. The method according to claim 11, wherein the second interconnection metal layer overlaps the second gate contact.
13. The method according to claim 11, wherein the first IMD layer comprises an ultra-low dielectric constant material layer.

- 14.** The method according to claim 13, wherein the second IMD layer comprises a TEOS-based oxide layer or a high-density plasma (HDP) oxide layer.
- 15.** The method according to claim 14, wherein the second interconnection metal layer is disposed in the second IMD layer.
- 16.** The method according to claim 14, wherein the first IMD layer extends onto a top surface of the second IMD layer.
- 17.** The method according to claim 16, wherein the second interconnection metal layer is disposed in the first IMD layer that extends onto the top surface of the second IMD layer.
- 18.** The method according to claim 11, wherein the first gate contact and the second gate contact comprise tungsten.
- 19.** The method according to claim 11, wherein the first gate and the second gate are metal gates.
- 20.** The method according to claim 11, wherein the first IMD layer and the second IMD layer are ultra-low dielectric constant material layer.
-