

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12416058
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Machado Amorim; Tiago et al.

Hot formed pre-coated steel part

Abstract

A hot formed pre-coated steel part includes a steel sheet precoated with a metallic coating and hot formed, the coating including: 2.0 to 24.0% by weight of zinc; 1.1 to 7.0% by weight of silicon; optionally from 0.5 to 3.0% by weight of magnesium when the amount of silicon is between 1.1 and 4.0%, and optionally additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; and a ratio Al/Zn by weight greater than 2.9, where a microstructure in the steel after said hot forming being martensitic or martensitic-bainitic or made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%.

Inventors: Machado Amorim; Tiago (Longeville les Metz, FR), Allely; Christian (Metz, FR), Grigorieva; Raisa (Metz, FR), Dussaussois; David (Homecourt, FR)

Applicant: ArcelorMittal (Luxembourg, LU)

Family ID: 1000008821227

Assignee: ArcelorMittal (Luxembourg, LU)

Appl. No.: 17/463128

Filed: August 31, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20210395853 A1	Dec. 23, 2021

Foreign Application Priority Data

WO	PCT/IB2015/001284	Jul. 30, 2015
----	-------------------	---------------

Related U.S. Application Data

continuation parent-doc US 15748395 US 11162153 WO PCT/IB2016/000983 20160711 child-doc
US 17463128

Publication Classification

Int. Cl.: **C21D9/46** (20060101); **B21D22/02** (20060101); **B32B15/01** (20060101); **C21D1/673** (20060101); **C21D6/00** (20060101); **C21D8/00** (20060101); **C22C21/02** (20060101); **C22C21/10** (20060101); **C23C2/12** (20060101); **C23C2/26** (20060101); **C23C2/28** (20060101); **C23C2/40** (20060101)

U.S. Cl.:

CPC **C21D9/46** (20130101); **B21D22/022** (20130101); **B32B15/012** (20130101); **C21D1/673** (20130101); **C21D6/004** (20130101); **C21D6/005** (20130101); **C21D6/008** (20130101); **C21D8/005** (20130101); **C22C21/02** (20130101); **C22C21/10** (20130101); **C23C2/12** (20130101); **C23C2/26** (20130101); **C23C2/261** (20220801); **C23C2/28** (20130101); **C23C2/29** (20220801); **C23C2/40** (20130101); C21D2211/002 (20130101); C21D2211/005 (20130101); C21D2211/008 (20130101)

Field of Classification Search

CPC: B21D (22/022); B32B (15/012); C21D (1/673); C21D (2211/002); C21D (2211/005); C21D (2211/008); C21D (6/004); C21D (6/005); C21D (6/008); C21D (8/005); C21D (9/46); C22C (21/02); C22C (21/10); C23C (2/12); C23C (2/26); C23C (2/28)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6635359	12/2002	Kurosaki et al.	N/A	N/A
7867344	12/2010	Kusumi et al.	N/A	N/A
8453482	12/2012	Maki et al.	N/A	N/A
8858735	12/2013	Kondo et al.	N/A	N/A
9034480	12/2014	Yoshida et al.	N/A	N/A
9074277	12/2014	Maki et al.	N/A	N/A
9234267	12/2015	Yoshida et al.	N/A	N/A
9296520	12/2015	Watakabi	N/A	N/A
11162153	12/2020	Machado Amorim et al.	N/A	N/A
2005/0142294	12/2004	Marutian et al.	N/A	N/A
2007/0163685	12/2006	Steel	N/A	N/A
2007/0271978	12/2006	Brandstatter et al.	N/A	N/A
2010/0068412	12/2009	Chaleix	N/A	N/A
2010/0221572	12/2009	Laurent et al.	N/A	N/A
2010/0282373	12/2009	Van Tol et al.	N/A	N/A
2010/0319426	12/2009	Pohl et al.	N/A	N/A

2011/0274945	12/2010	Corp	N/A	N/A
2011/0303328	12/2010	Kondo et al.	N/A	N/A
2012/0073351	12/2011	Maki et al.	N/A	N/A
2012/0085466	12/2011	Lupp et al.	N/A	N/A
2012/0085467	12/2011	Thirion	148/531	C22C 38/04
2012/0088115	12/2011	Smith	428/548	C23C 2/12
2012/0135263	12/2011	Kobayashi et al.	N/A	N/A
2012/0186705	12/2011	Sikora	148/714	B21D 37/16
2012/0267012	12/2011	Sohn et al.	N/A	N/A
2013/0206824	12/2012	Wakatabi	N/A	N/A
2013/0236739	12/2012	Yoshida et al.	N/A	N/A
2013/0295411	12/2012	Yoshida	428/659	C23C 28/322
2014/0027026	12/2013	Schwinghammer et al.	N/A	N/A
2014/0216612	12/2013	Laurent	148/531	C23C 2/26
2014/0377584	12/2013	Iasegawa et al.	N/A	N/A
2015/0007911	12/2014	Murakami	148/507	C22C 38/32
2015/0020562	12/2014	Yamanaka et al.	N/A	N/A
2015/0147589	12/2014	Bouaziz et al.	N/A	N/A
2015/0191813	12/2014	Maki et al.	N/A	N/A
2015/0284861	12/2014	Allely et al.	N/A	N/A
2016/0222484	12/2015	Koyer et al.	N/A	N/A
2017/0073792	12/2016	Hikida et al.	N/A	N/A
2018/0023177	12/2017	Rachiele et al.	N/A	N/A
2018/0044774	12/2017	Allely et al.	N/A	N/A
2018/0051366	12/2017	Ooi	N/A	C23C 2/28
2018/0195159	12/2017	Sohn et al.	N/A	N/A
2018/0216218	12/2017	Machado Amorim et al.	N/A	N/A
2018/0223386	12/2017	Machado Amorim et al.	N/A	N/A
2018/0223409	12/2017	Allely et al.	N/A	N/A
2019/0044774	12/2018	Crols	N/A	N/A
2019/0218651	12/2018	Allely et al.	N/A	N/A
2019/0271342	12/2018	Canourgues et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
1829816	12/2005	CN	N/A
101617059	12/2008	CN	N/A
101631880	12/2009	CN	N/A
102011082	12/2010	CN	N/A

102300707	12/2010	CN	N/A
102301014	12/2010	CN	N/A
102791901	12/2011	CN	N/A
103547687	12/2013	CN	N/A
104388870	12/2014	CN	N/A
2553128	12/2014	CN	N/A
10246164	12/2003	DE	C21D 1/673
202012000616	12/2011	DE	N/A
1134301	12/2000	EP	N/A
1225246	12/2010	EP	N/A
2644736	12/2012	EP	N/A
2695963	12/2013	EP	N/A
2839049	12/2016	EP	N/A
S464045	12/1970	JP	N/A
S60162763	12/1984	JP	N/A
H04293759	12/1991	JP	N/A
H10176238	12/1997	JP	N/A
11279735	12/1998	JP	N/A
H11279735	12/1998	JP	N/A
2000104153	12/1999	JP	N/A
2000328216	12/1999	JP	N/A
2001073108	12/2000	JP	N/A
2001115247	12/2000	JP	N/A
2001214280	12/2000	JP	N/A
2002012959	12/2001	JP	N/A
2002322527	12/2001	JP	N/A
2003251272	12/2002	JP	N/A
2004339530	12/2003	JP	N/A
2005060728	12/2004	JP	N/A
2005290418	12/2004	JP	N/A
2006051543	12/2005	JP	N/A
2006193776	12/2005	JP	N/A
2006218518	12/2005	JP	N/A
2006299377	12/2005	JP	N/A
2007182608	12/2006	JP	N/A
2007211276	12/2006	JP	N/A
2008038168	12/2007	JP	N/A
2008111189	12/2007	JP	N/A
2010070784	12/2009	JP	N/A
2010515830	12/2009	JP	N/A
2010229483	12/2009	JP	N/A
2010535636	12/2009	JP	N/A
4733522	12/2010	JP	N/A
2011152589	12/2010	JP	N/A
2012112010	12/2011	JP	N/A
2012516939	12/2011	JP	N/A
2015094006	12/2014	JP	N/A
2016539249	12/2015	JP	N/A
0146986	12/1997	KR	N/A

100317680	12/2000	KR	N/A
20040007718	12/2003	KR	N/A
20140119809	12/2013	KR	N/A
2403309	12/2009	RU	N/A
2466210	12/2011	RU	N/A
2544977	12/2014	RU	N/A
76547	12/2005	UA	N/A
WO 02/103073	12/2001	WO	N/A
WO 2010085983	12/2009	WO	N/A
WO 2010086186	12/2009	WO	N/A
WO2012137687	12/2011	WO	N/A
WO2013122004	12/2012	WO	N/A
WO2013156688	12/2012	WO	N/A
WO2014059475	12/2013	WO	N/A

OTHER PUBLICATIONS

Hauger A et al., “Flexibles Walzen Von Tailer Rolled Blanks//Flexible Rolling of Tailor Rolled Blanks”, Stahl und Eisen, Verlag Stahleisen, Jan. 1, 2006, pp. 21-23, vol. 126, No. 5, Dusseldorf, DE See English Abstract. cited by applicant

U.S. Appl. No. 17/463,142, filed Aug. 31, 2021, Allely et al., enclosed. cited by applicant

U.S. Appl. No. 17/463,187, filed Aug. 31, 2021, Allely et al., enclosed. cited by applicant

U.S. Appl. No. 17/463,217, filed Aug. 31, 2021, Allely et al., enclosed. cited by applicant

Spiekermann P, “Legierungen—ein besonderes patentrechtliches Problem?”, Mitteilungen Der Deutschen Patentanwaelte, Heymann, Koln, DE, (Jan. 1, 1993), vol. 34, ISSN 0026-6884, pp. 178-190, XP002152326 [A] 1-26 * p. 4-p. 5. cited by applicant

Primary Examiner: Wu; Jenny R

Attorney, Agent or Firm: Davidson Kappel LLC

Background/Summary

(1) This is a Continuation of U.S. Ser. No. 15/748,395, filed Jan. 29, 2018, which is a National Phase of International Patent Application PCT/IB2016/000983, filed Jul. 11, 2016 claiming priority to International Patent Application PCT/IB2015/001284, filed Jul. 30, 2015. All of the above applications are hereby incorporated by reference herein.

(1) The present invention relates to a method for the manufacture of a hardened part starting from a steel sheet coated with a metallic coating. The invention is particularly well suited for the manufacture of automotive vehicles.

BACKGROUND

(2) Zinc based coatings are generally used because they allow for a protection against corrosion thanks to barrier protection and cathodic protection. The barrier effect is obtained by the application of a metallic coating on steel surface. Thus, the metallic coating prevents the contact between steel and corrosive atmosphere. The barrier effect is independent from the nature of coating and substrate. On the contrary, sacrificial cathodic protection is based on the fact that zinc is a metal less noble than steel. Thus, if corrosion occurs, zinc is consumed preferentially to steel. Cathodic protection is essential in areas where steel is directly exposed to corrosive atmosphere, like cut edges where surrounding zinc will be consumed before steel.

(3) However, when heating steps are performed on such zinc coated steel sheets, for example press hardening or welding, cracks are observed in steel which spread from the coating. Indeed, occasionally, there is a reduction of metal mechanical properties due to the presence of cracks in coated steel sheet after heating steps. These cracks appear with the following conditions: high temperature; contact with a liquid metal having a low melting point (such as zinc) in addition to stress; heterogeneous diffusion of molten metal with substrate grain bulk and boundary. The designation for such phenomenon is liquid metal embrittlement (LME), also called liquid metal assisted cracking (LMAC).

(4) The patent application US2013/0206824 discloses a method for producing a steel component with a metallic anti-corrosion coating from a steel sheet comprising at least 0.4% by weight Mn. The sheet steel product is annealed in a continuous furnace under an annealing atmosphere containing up to 25% by volume H.sub.2, 0.1% to 10% by volume NH.sub.3, H.sub.2O, N.sub.2, and process-related impurities as the remainder, at a dew point between -50° C. and -5° C. at a temperature of 400 to 1100° C. for 5 to 600 s. The annealed steel sheet has a 5 to 200 µm thick nitration layer with a particle size finer than the particle size of the inner core layer. Once coated with a metallic protective layer, a blank is separated from the annealed steel sheet, heated to an austenitising temperature of 780 to 950° C., hot-formed, and cooled so that a hardened structure forms.

(5) At high temperature, the nitration layer allows for a minimization of risk of embrittlement in a sheet steel produced even when the sheet steel product is provided with a metallic coating. The metallic coating, which can be applied to the steel substrate, is based on Zn, Al, Zn—Al, Zn—Mg, Zn—Ni, Zn—Fe, Al—Mg, Al—Si, Zn—Al—Mg or Zn—Al—Mg—Si.

(6) However, from an industrial point of view, because of the presence of ammoniac gas during the nitriding treatment, lines have to be redesigned. Indeed, this step has to be done in a hermetic box to prevent the leakage of this gas. This hermetic box difficult to produce results in an increase of productivity costs. Moreover, it is difficult to find a material which can handle the corrosive ammoniac. Additionally, the nitriding treatment is added to the method for producing the coated part. Thus, the duration of this method is elongated resulting in a loss of productivity. Finally, the nitration layer inhibits the wettability of zinc coatings when hot-dip galvanization is realized.

SUMMARY OF THE INVENTION

(7) An object of the invention is to provide a method for the manufacture of a hardened part which does not have LME issues. An advantage of the present invention is, in particular, an easy to implement method in order to obtain a part which does not have LME issues generated by the hot-forming.

(8) The present invention provides a method for the manufacture of a hardened part comprising the following steps: A) the provision of a steel sheet pre-coated with a metallic coating comprising from 2.0 to 24.0% by weight of zinc, from 1.1 to 7.0% by weight of silicon, optionally from 1.1 to 8.0% by weight of magnesium when the amount of silicon is between 1.1 and 4.0%, and optionally additional elements chosen from Pb, Ni, Zr, or Hf, the content by weight of each additional element being less than 0.3% by weight, the balance being aluminum and unavoidable impurities and residuals elements from feeding ingots or from the passage of the steel sheet in the molten bath, wherein the ratio Al/Zn is above 2.9, B) the cutting of the coated steel sheet to obtain a blank; C) the thermal treatment of the blank at a temperature between 840 and 950° C. to obtain a fully austenitic microstructure in the steel, D) the transfer of the blank into a press tool, E) the hot-forming of the blank to obtain a part, F) the cooling of the part obtained at step E) in order to obtain a microstructure in steel being martensitic or martensite-bainitic or made of at least 75% of equiaxed ferrite, from 5 to 20% of martensite and bainite in amount less than or equal to 10%.

(9) The present invention also provides a part formed from the method above. The part may advantageously include a microstructure of the metallic coating comprising an interdiffusion layer Fe+Fe.sub.3Al, AlFe intermetallic phases containing dissolved Si and Zn and binary Zn—Al and

Si-rich phases.

(10) The present invention further provides use of the parts for the manufacture of an automotive vehicle.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Other characteristics and advantages of the invention will become apparent from the following detailed description of the invention.

(2) To illustrate the invention, various embodiments and trials of non-limiting examples will be described, particularly with reference to the following FIGURE:

(3) FIG. 1 illustrates a schematic representation of the composition according to the invention comprising from 2.0 to 24.0% of zinc, from 1.1 to 7.0% by weight of silicon and optionally magnesium when the amount of silicon is between 1.1 and 4.0%.

DETAILED DESCRIPTION

(4) The designation “steel” or “steel sheet” means a steel sheet for press hardening process having a composition allowing the part to achieve a higher tensile strength above or equal to 500 MPa, preferably above or equal to 1000 MPa, advantageously above or equal to 1500 MPa. The weight composition of steel sheet is preferably as follows: $0.03\% \leq C \leq 0.50\%$; $0.3\% \leq Mn \leq 3.0\%$; $0.05\% \leq Si \leq 0.8\%$; $0.015\% \leq Ti \leq 0.2\%$; $0.005\% \leq Al \leq 0.1\%$; $0\% \leq Cr \leq 2.50\%$; $0\% \leq S \leq 0.05\%$; $0\% \leq P \leq 0.1\%$; $0\% \leq B \leq 0.010\%$; $0\% \leq Ni \leq 2.5\%$; $0\% \leq Mo \leq 0.7\%$; $0\% \leq Nb \leq 0.15\%$; $0\% \leq N \leq 0.015\%$; $0\% \leq Cu \leq 0.15\%$; $0\% \leq Ca \leq 0.01\%$; $0\% \leq W \leq 0.35\%$, the balance being iron and unavoidable impurities from the manufacture of steel.

(5) For example, the steel sheet is 22MnB5 with the following composition: $0.20\% \leq C \leq 0.25\%$; $0.15\% \leq Si \leq 0.35\%$; $1.10\% \leq Mn \leq 1.40\%$; $0\% \leq Cr \leq 0.30\%$; $0\% \leq Mo \leq 0.35\%$; $0\% \leq P \leq 0.025\%$; $0\% \leq S \leq 0.005\%$; $0.020\% \leq Ti \leq 0.060\%$; $0.020\% \leq Al \leq 0.060\%$; $0.002\% \leq B \leq 0.004\%$, the balance being iron and unavoidable impurities from the manufacture of steel.

(6) The steel sheet can be Usibor®2000 with the following composition: $0.24\% \leq C \leq 0.38\%$; $0.40\% \leq Mn \leq 3\%$; $0.10\% \leq Si \leq 0.70\%$; $0.015\% \leq Al \leq 0.070\%$; $0\% \leq Cr \leq 2\%$; $0.25\% \leq Ni \leq 2\%$; $0.020\% \leq Ti \leq 0.10\%$; $0\% \leq Nb \leq 0.060\%$; $0.0005\% \leq B \leq 0.0040\%$; $0.003\% \leq N \leq 0.010\%$; $0.0001\% \leq S \leq 0.005\%$; $0.0001\% \leq P \leq 0.025\%$; it being understood that the contents of titanium and nitrogen satisfy $Ti/N > 3.42$; and that the contents of carbon, manganese, chromium and silicon satisfy:

(7) $2.6C + \frac{Mn}{5.3} + \frac{Cr}{13} + \frac{Si}{15} \geq 1.1\%$

the composition optionally comprising one or more of the following: $0.05\% \leq Mo \leq 0.65\%$; $0.001\% \leq W \leq 0.30\%$; $0.0005\% \leq Ca \leq 0.005\%$, the balance being iron and unavoidable impurities from the manufacture of steel.

(8) For example, the steel sheet is Ductibor®500 with the following composition: $0.040\% \leq C \leq 0.100\%$; $0.80\% \leq Mn \leq 2.00\%$; $0\% \leq Si \leq 0.30\%$; $0\% \leq S \leq 0.005\%$; $0\% \leq P \leq 0.030\%$; $0.010\% \leq Al \leq 0.070\%$; $0.015\% \leq Nb \leq 0.100\%$; $0.030\% \leq Ti \leq 0.080\%$; $0\% \leq N \leq 0.009\%$; $0\% \leq Cu \leq 0.100\%$; $0\% \leq Ni \leq 0.100\%$; $0\% \leq Cr \leq 0.100\%$; $0\% \leq Mo \leq 0.100\%$; $0\% \leq Ca \leq 0.006\%$, the balance being iron and unavoidable impurities from the manufacture of steel.

(9) Steel sheet can be obtained by hot rolling and optionally cold rolling depending on the desired thickness, which can be for example between 0.7 and 3.0 mm.

(10) The invention relates to a method for the manufacture of a hardened part which does not have LME issue. Firstly, this method comprises the provision of steel sheet pre-coated with a metallic coating comprising from 2.0 to 24.0% by weight of zinc, from 1.1 to 7.0% by weight of silicon, optionally from 1.1 to 8.0% by weight of magnesium when the amount of silicon is between 1.1 and 4.0%, and optionally additional elements chosen from Pb, Ni, Zr, or Hf, the content by weight

of each additional element being less than 0.3% by weight, the balance being aluminum and unavoidable impurities and residuals elements, wherein the ratio Al/Zn is above 2.9.

(11) The coating composition is illustrated FIG. 1. According to the invention, the coating comprises optionally from 1.1 to 8.0% by weight of magnesium when the amount of silicon is between 1.1 and 4.0%. The optional presence of magnesium is represented in grey in this FIGURE.

(12) Without willing to be bound by any theory, it seems that if these conditions are not met, LME issue appears because Zn-rich phases are in too high amount and liquid zinc can diffuse towards the steel/coating interface and create macro-cracks in the steel.

(13) Preferably, the metallic coating does not comprise elements selected among Cr, Mn, Ti, Ce, La, Nd, Pr, Ca, Bi, In, Sn and Sb or their combinations. In another preferred embodiment, the metallic coating does not comprise any of the following compounds: Cr, Mn, Ti, Ce, La, Nd, Pr, Ca, Bi, In, Sn and Sb. Indeed, without willing to be bound by any theory, it seems that when these compounds are present in the coating, there is a risk that the properties of the coating, such as electrochemical potential, are altered, because of their possible interactions with the essential elements of the coatings.

(14) Preferably, the ratio Al/Zn is between 5 and 9. Without willing to be bound by any theory, it has been found that when the ratio Al/Zn is not between 5 and 9, there is a risk that the decrease of LME issue is less important because zinc is no longer in solid solution in the aluminum matrix and Zn-rich phases start to form.

(15) Preferably, the ratio Zn/Si is between 2.9 and 8. Without willing to be bound by any theory, it has been found that when the ratio Zn/Si is not between 2.9 and 8, there is a risk that the decrease of LME issue is less important because the proportion of Zn-rich phases is a little too high in the coating

(16) Advantageously, the coating comprises from 2.0 to 5.0%, preferably 2.1 to 4.9% by weight of silicon. In another preferred embodiment, the coating comprises from 1.5 to 3.5% by weight of silicon. In another preferred embodiment, the coating comprises from 4.5 to 5.5% by weight of silicon.

(17) Preferably, the coating comprises from 5.0 to 19.0%, preferably 5.0 to 15.0%, advantageously from 10.0 to 15.0% by weight of zinc.

(18) Advantageously, when the amount of silicon is between 1.1 and 4.0% by weight, the coating can comprise from 0.5 to 3.0%, preferably from 1.0 to 2.9% by weight of magnesium. In another preferred embodiment, the coating comprises from 3.1 to 8.0%, preferably from 4.0 to 8% by weight of magnesium.

(19) Advantageously, the coating comprises above 71%, preferably above 76%, by weight of aluminum.

(20) The coating can be deposited by any methods known to the man skilled in the art, for example hot-dip galvanization process, electrogalvanization process, physical vapour deposition such as jet vapor deposition or sputtering magnetron. Preferably, the coating is deposited by hot-dip galvanization process. In this process, the steel sheet obtained by rolling is dipped in a molten metal bath.

(21) The bath comprises zinc, silicon, aluminum and optionally magnesium. It can comprise additional elements chosen from Pb, Ni, Zr, or Hf, the content by weight of each additional element being less than 0.3% by weight. These additional elements can improve among others ductibility, coating adhesion on the steel sheet.

(22) The bath can also contain unavoidable impurities and residuals elements from feeding ingots or from the passage of the steel sheet in the molten bath. Residual element can be iron with a content up to 3.0% by weight.

(23) The thickness of the coating is usually between 5 and 50 μm , preferably between 10 and 35 μm , advantageously between 12 and 18 μm or between 26 to 31 μm . The bath temperature is usually between 580 and 660° C.

(24) After the deposition of the coating, the steel sheet is usually wiped with nozzles ejecting gas on both sides of the coated steel sheet. The coated steel sheet is then cooled. Preferably, the cooling rate is above or equal to $15^{\circ}\text{C. s.sup.-1}$ between the beginning of the solidification and the end of the solidification. Advantageously, the cooling rate between the beginning and the end of the solidification is superior or equal to $20^{\circ}\text{C. s.sup.1}$.

(25) Then, a skin-pass can be realized and allows work hardening the coated steel sheet and giving it a roughness facilitating the subsequent shaping. A degreasing and a surface treatment can be applied in order to improve for example adhesive bonding or corrosion resistance.

(26) Then, the coated steel sheet is cut to obtain a blank. A thermal treatment is applied to the blank in a furnace under non protective atmosphere at an austenitization temperature T_m usually between 840 and 950°C. , preferably 880 to 930°C. Advantageously, said blank is maintained during a dwell time t_m between 1 to 12 minutes, preferably between 3 to 9 minutes. During the thermal treatment before the hot-forming, the coating forms an alloy layer having a high resistance to corrosion, abrasion, wear and fatigue.

(27) After the thermal treatment, the blank is then transferred to a hot-forming tool and hot-formed at a temperature between 600 and 830°C. The hot-forming comprises the hot-stamping and the roll-forming. Preferably, the blank is hot-stamped. The part is then cooled in the hot-forming tool or after the transfer to a specific cooling tool.

(28) The cooling rate is controlled depending on the steel composition, in such a way that the final microstructure after the hot-forming comprises mostly martensite, preferably contains martensite, or martensite and bainite, or is made of at least 75% of equiaxed ferrite, from 5 to 20% of martensite and bainite in amount less than or equal to 10%.

(29) Thus, a hardened part without LME according to the invention is obtained.

(30) Preferably, the microstructure of the coating of the part comprises an interdiffusion layer Fe+Fe.sub.3Al , AlFe intermetallic phases containing dissolved Si and Zn, binary Zn—Al and Si-rich phases. When magnesium is present in the coating, the microstructure comprises also Zn.sub.2Mg phase and/or Mg.sub.2Si phase.

(31) In a preferred embodiment, the part is a press hardened steel part having a variable thickness, i.e. the press hardened steel part of the invention can have a thickness which is not uniform but which can vary. Indeed, it is possible to achieve the desired mechanical resistance level in the zones which are the most subjected to external stresses, and to save weight in the other zones of the press hardened part, thus contributing to the vehicle weight reduction. In particular, the parts with non-uniform thickness can be produced by continuous flexible rolling, i.e. by a process wherein the sheet thickness obtained after rolling is variable in the rolling direction, in relationship with the load which has been applied through the rollers to the sheet during the rolling process.

(32) Thus, within the conditions of the invention, it is possible to manufacture advantageously vehicle parts with varying thickness in order to obtain for example a tailored rolled blank. Specifically, the part can be a front rail, a seat cross member, a side sill member, a dash panel cross member, a front floor reinforcement, a rear floor cross member, a rear rail, a B-pillar, a door ring or a shotgun.

(33) For automotive application, after phosphating step, the part is dipped in an e-coating bath. Usually, the thickness of the phosphate layer is between 1 and 2 μm and the thickness of the e-coating layer is between 15 and 25 μm , preferably inferior or equal to 20 μm . The cataphoresis layer ensures an additional protection against corrosion.

(34) After the e-coating step, other paint layers can be deposited, for example, a primer coat of paint, a basecoat layer and a top coat layer.

(35) Before applying the e-coating on the part, the part is previously degreased and phosphated so as to ensure the adhesion of the cataphoresis.

(36) The invention will now be explained in trials carried out for information only. They are not limiting.

EXAMPLES

(37) For all samples, steel sheets used are 22MnB5. The composition of the steel is as follows: C=0.2252%; Mn=1.1735%; P=0.0126%, S=0.0009%; N=0.0037%; Si=0.2534%; Cu=0.0187%; Ni=0.0197%; Cr=0.180%; Sn=0.004%; Al=0.0371%; Nb=0.008%; Ti=0.0382%; B=0.0028%; Mo=0.0017%; As=0.0023% et V=0.0284%.

(38) All coatings were deposited by hot-dip galvanization process.

Example 1: Cracking Resistance Test

(39) This test is used to determine the presence of cracks obtainable after the hot-forming during the press hardening process.

(40) Trials 1 to 10 were prepared and subjected to the Cracking resistance test.

(41) To this end, coated trials were cut in order to obtain a blank. Blanks were then heated at a temperature of 900° C. during a dwell time varying between 5 and 10 minutes. Blanks were transferred into a press tool and hot-stamped in order to obtain parts having an omega shape. Then, parts were cooled to obtain a hardening by martensitic transformation.

(42) Finally, the deformed section of parts was cut. Then, the presence of cracks was analyzed by SEM (Scanning Electron Microscopy). 0 means excellent, in other words, there is no cracks at all; 1 means that there are microcracks having a deep between 0 and 50 µm and 2 means very bad, in other words, there are macrocracks having a deep above 50 µm. Results are shown in the following Table 1:

(43) TABLE-US-00001 thermal treatment at 900° C. Dwell Dwell Coating Thickness time = 5 time = 10 Trials Al Si Zn Mg Al/Zn Zn/Si (µm) minutes minutes 1 81 9 10 — 8.1 1.1 27 2 2 2 77 9 10 4 7.7 1.1 27 2 1 3 73 9 10 8 7.3 1.1 27 2 2 4 76 9 15 — 5.1 1.7 27 2 2 5 79 5 15 1 5.3 3.0 27 2 2 6 78 5 15 2 5.2 3.0 27 2 2 7* 80 5 15 — 5.3 3.0 27 0 0 8* 83 2 15 — 5.6 7.5 27 0 0 9* 86 2 10 2 8.6 5.0 27 0 0 10* 88 2 10 — 8.8 5.0 27 0 0 *examples according to the invention.

(44) All Trials according to the invention (Trials 7 to 10) show excellent behavior during hot-stamping. Indeed, no crack appears with the parts according to the present invention in contrary to Trials 1 to 6.

Example 2: Tool Degradation Test

(45) This test is used to determine the presence of scratch and coating smearing in the press tool after the hot-stamping.

(46) Thus, the press tool was analyzed by naked eyes after the hot-stamping of Trials 1, 2, 4 and 7 to 10 prepared in Example 1. 0 means excellent, in other words, there is no tool degradation and no coating smearing in the press tool; 1 means that there are scratches and slight coating smearing in the press tool and 2 means very bad, in other words, there are heavy scratches and important coating smearing in the press tool. Results are shown in the following Table 2:

(47) TABLE-US-00002 Covering rate after a thermal treatment at 900° C. (%) Dwell Dwell Coating time = 5 time = 10 Trials Al Si Zn Mg Al/Zn Zn/Si minutes minutes 11 81 9 10 — 9.1 1.1 1 1 12 77 9 10 4 7.7 1.1 2 2 13 76 9 15 — 5.1 1.7 2 1 14* 80 5 15 — 5.3 3.0 0 0 15* 83 2 15 — 5.5 7.5 0 0 16* 86 2 10 2 8.6 5.0 0 0 17* 88 2 10 — 8.6 5.0 0 0 *examples according to the invention.

(48) Trials 14 to 17 according to the invention have an excellent behavior in a press tool in contrary to Trials 11 to 13.

Claims

1. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 2.0 to 24.0% by weight of zinc; 1.1 to 7.0% by weight of silicon; and optionally additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding

- ingots or from a passage of the steel sheet in a molten bath; a ratio Al/Zn by weight greater than 2.9; and a ratio Zn/Si by weight between 2.9 and 8; a microstructure in the steel sheet after hot forming being martensitic or martensitic-bainitic or made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%, wherein a thickness of the coating is between 10 and 50 μm , and the coating is free from magnesium.
2. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises at least one of the additional elements chosen from Pb, Ni, Zr, or Hf.
 3. The hot formed pre-coated steel part according to claim 1, wherein the ratio Al/Zn is between 5 and 9.
 4. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises from 2.0 to 4.0% by weight of silicon.
 5. The hot formed pre-coated steel part according to claim 4, wherein the coating comprises from 2.0 to 3.5% by weight of silicon.
 6. The hot formed pre-coated steel part according to claim 4, wherein the coating comprises from 5.0 to 10.0% by weight of zinc.
 7. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises from 2.1 to 4.9% by weight of silicon.
 8. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises from 1.5 to 3.5% by weight of silicon.
 9. The hot formed pre-coated steel part according to claim 8, wherein the coating comprises from 5.0 to 10.0% by weight of zinc.
 10. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises from 5.0 to 19.0% by weight of zinc.
 11. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises from 5.0 to 15.0% by weight of zinc.
 12. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises from 5.0 to 10.0% by weight of zinc.
 13. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises greater than 71% by weight of aluminum.
 14. The hot formed pre-coated steel part according to claim 1, wherein the coating comprises greater than 76% by weight of aluminum.
 15. The hot formed pre-coated steel part according to claim 1, wherein a thickness of the coating is between 12 and 50 μm .
 16. The hot formed pre-coated steel part according to claim 15, wherein the thickness is between 10 and 35 μm .
 17. The hot formed pre-coated steel part according to claim 15, wherein the thickness is between 12 and 18 μm .
 18. The hot formed pre-coated steel part according to claim 15, wherein the thickness is between: 26 and 31 μm .
 19. The hot formed pre-coated steel part according to claim 1, wherein the coating does not comprise any of Cr, Mn, Ti, Ce, La, Nd, Pr, Bi, In, Sn and Sb.
 20. The hot formed pre-coated steel part according to claim 1, wherein the coating does not include In and the coating does not include Sn.
 21. The hot formed pre-coated steel part according to claim 1, wherein the microstructure of the metallic coating comprises an interdiffusion layer Fe+Fe.sub.3Al, AlFe intermetallic phases containing dissolved Si and Zn, binary Zn-Al and Si-rich phases.
 22. The hot formed pre-coated steel part according to claim 21, wherein the microstructure of the metallic coating comprises at least one of a Zn.sub.2Mg phase or a Mg.sub.2Si phase.
 23. The hot formed pre-coated steel part according to claim 1, wherein the part is a press hardened steel part having a variable thickness.

24. The hot formed pre-coated steel part according to claim 23, wherein the variable thickness is produced by a continuous flexible rolling process.
25. The hot formed pre-coated steel part according to claim 1, wherein the part is a tailored rolled blank.
26. The hot formed pre-coated steel part according to claim 1 wherein the part is a front rail, a seat cross member, a side sill member, a dash panel cross member, a front floor reinforcement, a rear floor cross member, a rear rail, a B-pillar, a door ring or a shotgun.
27. The hot formed pre-coated steel part according to claim 1 wherein the steel sheet has a base made of 22MnB5 steel.
28. The hot formed pre-coated steel part according to claim 1 wherein the steel sheet has a base with a composition by weight percentage including: $24\% \leq C \leq 0.38\%$; $0.40\% \leq Mn \leq 3\%$; $0.10\% \leq Si \leq 0.70\%$; $0.015\% \leq Al \leq 0.070\%$; $0\% \leq Cr \leq 2\%$; $0.25\% \leq Ni \leq 2\%$; $0.020\% \leq Ti \leq 0.10\%$; $0\% \leq Nb \leq 0.060\%$; $0.0005\% \leq B \leq 0.0040\%$; $0.003\% \leq N \leq 0.010\%$; $0.0001\% \leq S \leq 0.005\%$; $0.0001\% \leq P \leq 0.025\%$; it being understood that the contents of titanium and nitrogen satisfy $Ti/N > 3.42$, and that the contents of carbon, manganese, chromium and silicon satisfy $2.6C + Mn/5.3 + Cr/13 + Si/15 > 1.1\%$, the composition optionally comprising one or more of the following: $0.05\% \leq Mo \leq 0.65\%$; $0.001\% \leq W \leq 0.30\%$; $0.0005\% \leq Ca \leq 0.005\%$, a balance of the steel sheet base composition being iron and unavoidable impurities from manufacture.
29. The hot formed pre-coated steel part according to claim 1, wherein the steel sheet has a base with a composition by weight percentage including: $0.040\% \leq C \leq 0.100\%$; $0.80\% \leq Mn \leq 2.00\%$; $0\% \leq Si \leq 0.30\%$; $0\% \leq S \leq 0.005\%$; $0\% \leq P \leq 0.030\%$; $0.010\% \leq Al \leq 0.070\%$; $0.015\% \leq Nb \leq 0.100\%$; $0.030\% \leq Ti \leq 0.080\%$; $0\% \leq N \leq 0.009\%$; $0\% \leq Cu \leq 0.100\%$; $0\% \leq Ni \leq 0.100\%$; $0\% \leq Cr \leq 0.100\%$; $0\% \leq Mo \leq 0.100\%$; $0\% \leq Ca \leq 0.006\%$, a balance of the steel sheet base composition being iron and unavoidable impurities from manufacture.
30. The hot formed pre-coated steel part according to claim 1, wherein the steel sheet has a base with a composition by weight percentage including: $0.03\% \leq C \leq 0.50\%$; $0.3\% \leq Mn \leq 3.0\%$; $0.05\% \leq Si \leq 0.8\%$; $0.015\% \leq Ti \leq 0.2\%$; $0.005\% \leq Al \leq 0.1\%$; $0\% \leq Cr \leq 2.50\%$; $0\% \leq S \leq 0.05\%$; $0\% \leq P \leq 0.1\%$; $0\% \leq B \leq 0.010\%$; $0\% \leq Ni \leq 2.5\%$; $0\% \leq Mo \leq 0.7\%$; $0\% \leq Nb \leq 0.15\%$; $0\% \leq N \leq 0.015\%$; $0\% \leq Cu \leq 0.15\%$; $0\% \leq Ca \leq 0.01\%$; $0\% \leq W \leq 0.35\%$, a balance of the steel sheet base composition being iron and unavoidable impurities from the manufacture of steel.
31. The hot formed pre-coated steel part according to claim 1, wherein the coating after hot forming and subsequent cooling has no cracks.
32. An automotive vehicle comprising the part according to claim 1.
33. The hot formed pre-coated steel part according to claim 1, wherein the coating does not include Ca.
34. The hot formed pre-coated steel part according to claim 1, wherein the ratio Al/Zn is 5.6 or less.
35. The hot formed pre-coated steel part according to claim 1, wherein the coating includes 10 to 15% zinc, 2 to 5% silicon, a ratio Al/Zn between 5.3 and 8.8%; and a ratio Zn/Si by weight between 3 and 7.5.
36. The hot formed pre-coated steel part according to claim 1, wherein the coating includes, by weight, $10\% < \text{zinc} \leq 24\%$.
37. The hot formed pre-coated steel part according to claim 1, wherein the coating includes 1.1 to 4.9% by weight of silicon.
38. The hot formed pre-coated steel part according to claim 1, wherein the coating includes 1.1 to 2% by weight of silicon, or 15 to 24.0% by weight of zinc.
39. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 2.0 to 24.0% by weight of zinc; 1.1 to 7.0% by weight of silicon; 0 to 3.0% by weight of magnesium, with the proviso that the coating includes from 0.5 to 3.0% by weight of magnesium when the amount of silicon is between 1.1 and 4.0%, and at least one additional elements chosen from Pb, Ni, Zr or Hf,

a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; and a ratio Al/Zn by weight between 8.6 and 9; and a ratio Zn/Si by weight between 2.9 and 8, wherein the microstructure in the steel sheet after hot forming is made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%, and a thickness of the coating is between 10 and 50 μm .

40. The hot formed pre-coated steel part according to claim 39, wherein the coating comprises from 0.5 to 3.0% by weight of magnesium.

41. The hot formed pre-coated steel part according to claim 40, wherein the coating comprises from 5.0 to 10.0% by weight of zinc.

42. The hot formed pre-coated steel part according to claim 41, wherein the coating comprises greater than 71% by weight of aluminum.

43. The hot formed pre-coated steel part according to claim 41, wherein the coating comprises greater than 76% by weight of aluminum.

44. The hot formed pre-coated steel part according to claim 39, wherein the coating comprises from 1.0 to 2.9% by weight of magnesium.

45. The hot formed pre-coated steel part according to claim 39, wherein the coating comprises from 1.5 to 3.5% by weight of silicon, from 5.0 to 10.0% by weight of zinc, and 1.0 to 2.9% by weight of magnesium.

46. The hot formed pre-coated steel part according to claim 45, wherein the coating comprises greater than 71% by weight of aluminum.

47. The hot formed pre-coated steel part according to claim 45, wherein the coating comprises greater than 76% by weight of aluminum.

48. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 2.0 to 24.0% by weight of zinc; 1.1 to 7.0% by weight of silicon; and optionally additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; a ratio Al/Zn by weight greater than 2.9; a ratio Zn/Si by weight between 2.9 and 8; a microstructure in the steel sheet after hot forming being made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%, wherein a thickness of the coating is between 10 and 50 μm , and the coating is free from magnesium.

49. The hot formed pre-coated steel part according to claim 48, wherein the coating includes 1.1 to 2% by weight of silicon, or 15 to 24.0% by weight of zinc.

50. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 2.0 to 24.0% by weight of zinc; 1.1 to 7.0% by weight of silicon; and optionally additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; and a ratio Al/Zn by weight greater than 2.9; a microstructure in the steel sheet after hot forming being martensitic or martensitic-bainitic or made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%, wherein the steel sheet has a base with a carbon content by weight of between 0.24% and 0.38%, wherein a thickness of the coating is between 10 and 50 μm , and the coating is free from magnesium.

51. The hot formed pre-coated steel part according to claim 50, wherein the coating includes 1.1 to 2% by weight of silicon, or 15 to 24.0% by weight of zinc.

52. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 2.0 to 24.0%

by weight of zinc; 1.1 to 7.0% by weight of silicon; at least one additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; and a ratio Zn/Si by weight is between 7.5 and 8; a microstructure in the steel sheet after hot forming being made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%, wherein the steel sheet has a base with a carbon content by weight of between 0.24% and 0.38%, wherein a thickness of the coating is between 10 and 50 μm , and the coating includes $0.5 \leq \text{Mg} \leq 3.0\%$.

53. The hot formed pre-coated steel part according to claim 52, wherein the coating includes 1.1 to 2% by weight of silicon, or 15 to 24.0% by weight of zinc.

54. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 2.0 to 24.0% by weight of zinc; 1.1 to 7.0% by weight of silicon; and optionally additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; a ratio Al/Zn by weight greater than 2.9; and a ratio Zn/Si by weight between 2.9 and 8; a microstructure in the steel sheet after hot forming being martensitic or martensitic-bainitic or made of at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%; and wherein the hot formed pre-coated steel part exhibits no microcracks having a depth greater than 50 μm ; and wherein a thickness of the coating is between 10 and 50 μm , and the coating is free from magnesium.

55. The hot formed pre-coated steel part according to claim 54, wherein the coating includes 10 to 15% zinc, 2 to 5% silicon, a ratio Al/Zn between 5.3 and 8.8%; and a ratio Zn/Si by weight between 3 and 7.5.

56. A hot formed pre-coated steel part, comprising a steel sheet precoated with a metallic coating and then hot formed into the hot formed pre-coated steel part, the coating including: 5 to 10% by weight of zinc; 2 to 5% by weight of silicon; at least on additional elements chosen from Pb, Ni, Zr or Hf, a content by weight of each additional element being less than 0.3% by weight, a balance being aluminum, unavoidable impurities and residual elements resulting from feeding ingots or from a passage of the steel sheet in a molten bath; a ratio Al/Zn by weight between 5.3 and 8.8%; and a ratio Zn/Si by weight between 3 and 7.5; a microstructure in the steel sheet after hot forming being at least 75% of equiaxed ferrite, 5 to 20% of martensite and bainite in an amount less than or equal to 10%; and wherein the hot formed pre-coated steel part exhibits no microcracks having a depth greater than 50 μm , wherein a thickness of the coating is between 10 and 50 μm , and the coating includes more than 0 and less than 3.0% by weight of magnesium, with the proviso that the coating includes from 0.5 to 3.0% by weight of magnesium when the amount of silicon is between 1.1 and 4.0%.

57. The hot formed pre-coated steel part according to claim 56, wherein the coating includes 1.1 to 4.9% by weight of silicon.
