

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12417921
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Rai; Shiva et al.

Methods and apparatus for in-situ protection of etched surfaces

Abstract

Methods and apparatus for processing a photonic device are provided herein. For example, methods include etching, using a plasma etch process that uses a first gas, a first epitaxial layer of material of the photonic device comprising a base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}$), aluminum indium gallium phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{P}_{0.5}$), aluminum indium gallium nitride ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{N}_{0.5}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}\text{P}_{0.5}$), depositing, using a plasma deposition process that uses a second gas different from the first gas, a first dielectric layer over etched sidewalls of the first epitaxial layer of material, etching, using the first gas, a second epitaxial layer of material of the photonic device, and depositing, using the second gas, a second dielectric layer over etched sidewalls of the second epitaxial layer of material.

Inventors:	Rai; Shiva (Fremont, CA), Granados; Alfredo (San Antonio, TX)
Applicant:	APPLIED MATERIALS, INC. (Santa Clara, CA)
Family ID:	1000008821207
Assignee:	APPLIED MATERIALS, INC. (Santa Clara, CA)
Appl. No.:	17/116335
Filed:	December 09, 2020

Prior Publication Data

Document Identifier	Publication Date
US 20220181160 A1	Jun. 09, 2022

Publication Classification

Int. Cl.: **H01L21/306** (20060101); **H01J37/32** (20060101); **H01L21/67** (20060101); **H10F71/00** (20250101); **H10F77/124** (20250101); **H10F77/14** (20250101); **H10F77/30** (20250101); **H10H20/01** (20250101); **H10H20/812** (20250101); **H10H20/821** (20250101); **H10H20/824** (20250101); **H10H20/825** (20250101); **H10H20/84** (20250101)

U.S. Cl.:

CPC **H01L21/30621** (20130101); **H01J37/32449** (20130101); **H01L21/67069** (20130101); **H10F71/1272** (20250101); **H10F71/1274** (20250101); **H10F71/1276** (20250101); **H10F77/1248** (20250101); **H10F77/12485** (20250101); **H10F77/146** (20250101); **H10F77/147** (20250101); **H10F77/306** (20250101); **H10F77/311** (20250101); **H10H20/0133** (20250101); **H10H20/01335** (20250101); **H10H20/812** (20250101); **H10H20/821** (20250101); **H10H20/824** (20250101); **H10H20/825** (20250101); **H10H20/84** (20250101); H01J2237/332 (20130101); H01J2237/3341 (20130101); H10H20/034 (20250101)

Field of Classification Search

CPC: H01L (21/30621); H01L (21/67069); H01L (31/02161); H01L (31/02167); H01L (31/03046); H01L (31/03048); H01L (31/035236); H01L (31/035281); H01L (31/1844); H01L (31/1848); H01L (31/1852); H01L (33/0066); H01L (33/007); H01L (33/06); H01L (33/24); H01L (33/30); H01L (33/32); H01L (33/44); H01L (2933/0025); H01J (37/32449); H01J (2237/332); H01J (2237/3341); H10H (20/821); H10H (20/0133); H10H (20/825); H10H (20/824); H10H (20/84); H10H (20/01335); H10H (20/812); H10H (20/034); H10F (77/146); H10F (77/147); H10F (77/1248); H10F (71/1276); H10F (77/12485); H10F (77/311); H10F (71/1272); H10F (71/1274); H10F (77/306)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5501893	12/1995	Laermer et al.	N/A	N/A
6867086	12/2004	Chen et al.	N/A	N/A
7224015	12/2006	Skotnicki	257/306	H10B 12/033
8133797	12/2011	Van Schravendijk et al.	N/A	N/A
9543148	12/2016	Hudson et al.	N/A	N/A
9611544	12/2016	LaVoie	N/A	H01L 21/02164
2008/0142483	12/2007	Hua et al.	N/A	N/A
2013/0020589	12/2012	Yu	257/E33.057	H01L 33/0093
2015/0364611	12/2014	Funch	257/532	H01L 29/0688
2019/0043732	12/2018	Eason	N/A	H10B 43/27
2020/0091224	12/2019	Bono	N/A	H10F 39/103

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2576108	12/2019	GB	N/A

OTHER PUBLICATIONS

https://en.wikipedia.org/wiki/Deep_reactive-ion_etching#Bosch_process. cited by applicant

Primary Examiner: Richards; Norman D

Assistant Examiner: Winters; Sean Ayers

Attorney, Agent or Firm: Moser Taboada

Background/Summary

(1) Embodiments of the present disclosure generally relate to a methods and apparatus for processing a substrate.

BACKGROUND

(2) Plasma etching processes (e.g., reactive-ion etching (RIE)) used for etching substrates (e.g., semiconductor devices or layers) are a known. During plasma etching, however, etched sidewalls of a substrate to which the plasma etching is being performed can become charged as a result of the plasma, which, in turn, can result in surface damage to the sidewalls. Conventional methods and apparatus sometimes deposit a passivation layer after the etching process is completed to try and recover the surfaces of the sidewalls. The effectiveness of using such methods and apparatus can depend on the material being etched, amount of surface damage to the sidewalls, and an efficacy of the passivation layer in neutralizing surface charges of the sidewalls. Moreover, passivation is a relatively complex process that can increase overall semiconductor device fabrication cost.

SUMMARY

(3) Methods and apparatus for processing a substrate are provided herein. For example, in some embodiments, a method of processing a photonic device includes etching, using a plasma etch process that uses a first gas, a first epitaxial layer of material of the photonic device comprising a

base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}$), aluminum indium gallium phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{P}_{0.5}$), aluminum indium gallium nitride ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{N}_{0.5}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}\text{P}_{0.5}$), depositing, using a plasma deposition process that uses a second gas different from the first gas, a first dielectric layer over etched sidewalls of the first epitaxial layer of material, etching, using the first gas, a second epitaxial layer of material of the photonic device, and depositing, using the second gas, a second dielectric layer over etched sidewalls of the second epitaxial layer of material.

(4) In accordance with at least some embodiments, a non-transitory computer readable storage medium having instructions stored thereon that, when executed by a processor, perform a method of processing a photonic device having one or more epitaxially deposited layers. The method includes etching, using a plasma etch process that uses a first gas, a first epitaxial layer of material of the photonic device comprising a base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}$), aluminum indium gallium phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{P}_{0.5}$), aluminum indium gallium nitride ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{N}_{0.5}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}\text{P}_{0.5}$), depositing, using a plasma deposition process that uses a second gas different from the first gas, a first dielectric layer over etched sidewalls of the first epitaxial layer of material, etching, using the first gas, a second epitaxial layer of material of the photonic device, and depositing, using the second gas, a second dielectric layer over etched sidewalls of the second epitaxial layer of material.

(5) In accordance with at least some embodiments, an apparatus for processing a photonic device having one or more epitaxially deposited layers includes a plasma processing chamber configured to etch, using a first gas, a first epitaxial layer of material and a second epitaxial layer of material of the photonic device, the photonic device comprising a base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}$), aluminum indium gallium phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{P}_{0.5}$), aluminum indium gallium nitride ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{N}_{0.5}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{0.5}\text{In}_{0.5}\text{Ga}_{0.5}\text{As}_{0.5}\text{P}_{0.5}$), and deposit, using a second gas different from the first gas, a first dielectric layer over etched sidewalls of the first epitaxial layer of material and a second dielectric layer over etched sidewalls of the second epitaxial layer of material.

(6) Other and further embodiments of the present disclosure are described below.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Embodiments of the present disclosure, briefly summarized above and discussed in greater detail below, can be understood by reference to the illustrative embodiments of the disclosure depicted in the appended drawings. However, the appended drawings illustrate only typical embodiments of the disclosure and are therefore not to be considered limiting of scope, for the disclosure may admit to other equally effective embodiments.
- (2) FIG. 1 is a schematic side view of a system in accordance with at least some embodiments of the present disclosure.
- (3) FIGS. 2A-2E are diagrams of a substrate in accordance with at least some embodiments of the present disclosure.
- (4) FIG. 3 is a flowchart of a method for processing the substrate of FIG. 2 in accordance with at least some embodiments of the present disclosure.
- (5) FIGS. 4A and 4B are diagrams of photonic devices fabricated using the method of FIG. 3 in accordance with at least some embodiments of the present disclosure.

(6) To facilitate understanding, identical reference numerals have been used, where possible, to designate identical elements that are common to the figures. The figures are not drawn to scale and may be simplified for clarity. Elements and features of one embodiment may be beneficially incorporated in other embodiments without further recitation.

DETAILED DESCRIPTION

(7) Embodiments of methods and apparatus for in-situ protection of etched surfaces are provided herein. For example, in at least some embodiments, one or more dielectric layers of material can be periodically deposited in-situ during an etching process performed on one or more layers of material disposed on a substrate (e.g., semiconductor layers used to form semiconductor devices such as photonic devices including, but not limited to, LEDs, lasers, photodetector, solar cells, and the like, which can have high aspect ratio etch features). The one or more dielectric layers are configured to cover the sidewalls of the feature being etched into the substrate, thus protecting the previously etched sidewalls from being exposed to plasma used as the etching process continues to form the feature. The methods and apparatus described herein can create substrates with minimal to no damage to the sidewalls during an etching process thereto and can reduce, if not eliminate the need to separately deposit a passivation layer. Additionally, mitigating surface damage on the substrate sidewalls can improve quantum efficiencies of photonic devices. Moreover, periodically depositing the dielectric layers of material on the etched surfaces of the sidewall during the etching process avoids creating charged surfaces on the etched sidewalls near the active region (e.g., multiple quantum wells (MQW)) of the substrate (e.g., semiconductor device or photonic device).

(8) FIG. 1 is a schematic of a system **100** in accordance with at least some embodiments of the present disclosure. The system **100** can be configured to perform one or more plasma processes on a substrate in a single processing chamber. e.g., a plasma processing chamber. For example, the system **100** can include plasma processing chamber configured to perform one or more etching processes (e.g., a reactive ion etch process) and to perform one or more plasma deposition processes (e.g., chemical vapor deposition).

(9) The system **100** includes a processing chamber **102** including a chamber body **105**, which can be grounded. Process gases are supplied from a gas source(s) **129** connected to the chamber body **105** through a mass flow controller **149** to an inner volume **103** (e.g., a processing region) of the processing chamber **102**.

(10) The processing chamber **102** can be evacuated via an exhaust valve **151** connected to a high capacity vacuum pump **155**. When plasma power is applied to the processing chamber **102**, a plasma **136** can be formed in the inner volume **103** over a substrate **110** to perform an etching process and/or a plasma deposition process.

(11) A plasma bias source **125** (e.g., RF power source or DC power source) is coupled to an electrostatic chuck (ESC) **142** to energize the plasma. In at least some embodiments, the plasma bias source **125** is an RF power source. The plasma bias source **125** can provide bias power at a frequency from about 400 kHz to about 60 MHz, and may be, for example, at about 13.56 MHz. The plasma bias source **125** can be coupled to an RF match network (not shown) and to a lower electrode (not shown, e.g., a chucking electrode) via a power conduit **128**. Additionally, in at least some embodiments, the processing chamber **102** can include a second plasma bias power (not shown, e.g., RF power source or DC power source). For example, if the second plasma source is a second RF power source, the second RF power source can also be connected to the RF match network. The second plasma bias power can operate at about 2 MHz to about 60 MHz. and may be, for example, at about 2 MHz.

(12) A plasma source power **131** is coupled through another match network (not shown) to provide high frequency source power to inductively or capacitively energize the plasma **136**. The plasma source power **131** may have a higher frequency than the plasma bias source **125**, such as between 100 and 180 MHz, and may, for example, be about 162 MHz. In at least some embodiments, the plasma can be created using one or more gases suitable for performing a plasma etch process

and/or a plasma deposition process (e.g., argon, bromine, carbon, chlorine, nitrogen, oxygen, or other suitable gas). The plasma is directed to a surface of the substrate **110** via, for example, a source **135** (e.g., a showerhead).

(13) The substrate **110** can be loaded through an opening **115** defined through the chamber body **105**. The substrate **110** (e.g., such as a semiconductor wafer or die) may be any wafer, substrate, or other material employed in the semiconductor processing art. For example, in at least some embodiments, the substrate can include layers of p-type material and n-type material that can be disposed near active regions (e.g., MQW) of the substrate **110**. The substrate **110** can be loaded onto a top surface of a dielectric layer **145** of the ESC **142**. A clamp electrode (not shown) can be embedded in the dielectric layer **145** and can be coupled to a source of bias power **179** to provide an electrostatic force to clamp the substrate **110** to the dielectric layer **145**.

(14) One or more cooling plates can be provided on one or more components of the processing chamber **102**. For illustrative purposes, cooling plates **144a**, **144b** are shown provided respectively on the source **135** and the ESC **142**. The cooling plates **144a**, **144b** can include one or more coolant channels (not shown) that receive coolant via one or more inlet channels (not shown) and that release the coolant via one or more output channels (not shown). In at least some embodiments, the inlet channel, which is connected to a coolant supply line **152** of a heat exchanger **150**, is connected to the first coolant output line **146** of a proportional bypass valve (PBV) **140** for receiving the coolant and the output channel is connected to a coolant return line **154** of the heat exchanger **150**, which is connected to the second coolant output line **148** of the PBV **140**. In at least some embodiments, the each of the cooling plates **144a**, **144b** can be connected to the same heat exchanger **150** (HTX/chillers), as illustrated in FIG. 1. Alternatively, each of the cooling plates **144a**, **144b** can be connected to separate heat exchangers. A flow rate of the thermal fluid or heat transfer fluid (e.g., coolant) through the one or more coolant channels in the cooling plates **144a**, **144b** of the source **135** and ESC **142** is controlled by the PBV **140**.

(15) A temperature controller **130** is coupled to the heat exchanger **150** and the PBV **140**. For example, the PBV **140** can be controlled by the temperature controller **130** to independently control a rate of flow of the coolant to each of the one or more coolant channels in the cooling plates **144a**, **144b**. The temperature controller **130** may also control the temperature set point used by the heat exchanger **150** to cool or heat the thermal fluid. The temperature controller **130** is also coupled to one or more temperature sensors (probes) **143**, which may be in or on an upper plate (not shown) of the ESC **142**.

(16) To facilitate control of the processing chamber **102**, the processing chamber **102** includes a controller **170**. The controller **170** includes a central processing unit (CPU) **172**, which may be one of any form of general-purpose computer processor that can be used in an industrial setting, such as a programmable logic controller (PLC), for controlling various chambers and sub-processors. A memory **173** is coupled to the CPU **172**, and the memory **173** can be non-transitory computer readable storage medium and may be one or more of readily available memory such as random access memory (RAM), read only memory (ROM), floppy disk drive, hard disk, or any other form of digital storage, local or remote. Support circuits **174** (e.g., I/O circuits) including one or more of power supplies, clocks, cache, etc. are coupled to the CPU **172** for supporting the processor in a conventional manner. Charged species generation, heating, and other processes are generally stored in the memory **173**, typically as software routine. The software routine may also be stored and/or executed by a second CPU (not shown) that is remotely located from the processing chamber **102** being controlled by the CPU **172**.

(17) The memory **173** is in the form of non-transitory computer-readable storage media that contains instructions which when executed by the CPU **172** facilitates the operation of the processing chamber **102** (e.g., perform a method of processing a substrate). The instructions in the memory **173** are in the form of a program product such as program code that implements the methods described herein. The program code may conform to any one of a number of different

programming languages. The program(s) of the program product define functions of the embodiments (including the methods described herein). Illustrative computer-readable storage media include, but are not limited to: (i) non-writable storage media (e.g., read-only memory devices within a computer such as CD-ROM disks readable by a CD-ROM drive, flash memory, ROM chips, or any type of solid-state non-volatile semiconductor memory) on which information is permanently stored; and (ii) writable storage media (e.g., floppy disks within a diskette drive or hard-disk drive or any type of solid-state random-access semiconductor memory) on which alterable information is stored.

(18) Additionally, the controller **170** is configured to perform etch control and deposition control using one or more control algorithms which can be stored in the memory **173**. For example, in at least some embodiments, etch control and deposition control algorithms used by the controller **170** can be configured to control an etch depth into one or more layers of a substrate, a thickness of a material to be deposited atop/on one or more layers (e.g., a top layer, bottom layer, an exposed sidewall, etc.) of a substrate, deposition angles, flow rate of process gas(es) used for etching and/or deposition, gas flow sequencing, process chamber pressure, RF/DC power, RF/DC bias, etc., as described in greater detail below.

(19) FIGS. 2A-2E are diagrams of a substrate **200** (e.g., a semiconductor device comprising epitaxially deposited layers) in accordance with at least some embodiments of the present disclosure, and FIG. 3 is a flowchart of a method **300** for processing the substrate **200** (e.g., processing a photonic device, such as creating trenches between adjacent photonic devices) of FIG. 2 in accordance with at least some embodiments of the present disclosure. In at least some embodiments, the method **300** can be used for accessing a contact layer or for singulating a die on a substrate (wafer). For illustrative purposes, the method **300** is described herein using the system **100** of FIG. 1, which is configured to perform both an etching process and deposition process in a single processing chamber for processing the semiconductor device, thus mitigating the impact of sidewall etch damage on an optical efficiency of an optical device. As noted above, one or more variables can be controlled, for example, by the controller **170**, to optimize the method **300**. For example, a type of process gas(es) used, RF/DC power, RF/DC bias, process chamber pressure, etch depth, deposition thickness, etc. can all be controlled by the controller **170** to achieve a specific outcome. For example, in at least some embodiments, a sidewall profile and angle can be tuned for a required substrate aspect ratio by adjusting, for example, a gas flow sequencing during an etching process and/or deposition process. In addition to gas flow, reduced pressure and increase ion energy are also key parameters that would further contribute to tuning sidewall profile and angle.

(20) At **302**, using a plasma etch process, a first layer of material of the substrate **200** (e.g., a semiconductor wafer or die) comprising a plurality of layers (e.g., a stack) can be etched to form one or more features, e.g., via, trench, dual damascene, etc. The features can be etched into the substrate **200** using a suitable masking layer (not shown), such as a photoresist or hard mask layer. For example, and as depicted in FIG. 2A, in at least some embodiments, the substrate **200** can include a layer of p-type material **204** (e.g., a first epitaxial layer of material such as aluminum indium gallium arsenide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{As}$), aluminum indium gallium phosphide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{P}$), aluminum indium gallium nitride ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{N}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{As}_{\text{sub.z}}\text{P}_{\text{sub.1-z}}$)), an active layer **206**, e.g., an MQW formed from one or more of the p-type materials **204** such as, for example, aluminum indium gallium arsenide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{As}$), aluminum indium gallium phosphide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{P}$), aluminum indium gallium nitride ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{N}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{As}_{\text{sub.z}}\text{P}_{\text{sub.1-z}}$), and a layer of n-type material **202** (e.g., a second epitaxial layer of material such as aluminum indium gallium arsenide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{As}$), aluminum indium gallium phosphide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{P}$), aluminum indium

gallium nitride ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{N}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{\text{sub.x}}\text{In}_{\text{sub.y}}\text{Ga}_{\text{sub.1-x-y}}\text{As}_{\text{sub.z}}\text{P}_{\text{sub.1-z}}$). The layer of n-type material **202**, layer of p-type material **204**, and active layer **206** can be configured in one or more variations. For example, the layer of p-type material **204** can be a top layer, the layer of n-type material **202** can be a bottom layer disposed atop a base layer **201** (e.g., comprising at least one of silicon, germanium, sapphire, gallium arsenide (GaAs), indium phosphide (InP), etc.) of the substrate **200**, and the active layer **206** can be disposed between the n-type material **202** and the layer of p-type material **204**.

Alternatively, the n-type material **202** can be the top layer and the layer of p-type material **204** can be the bottom layer and the active layer **206** can again be disposed between the n-type material **202** and the layer of p-type material **204**. The layer of n-type material **202**, layer of p-type material **204**, and active layer **206** of the substrate **200** can be used to form one or more photonic devices, e.g., comprising an LED, a laser, a photodetector, a solar cell, or the like. For example, each photonic device comprises an n-layer, an active layer and a p-layer stacked to make a complete photonic device. The materials used in the three layers can be different depending on the photonic device design and application. In at least some embodiments, the layer of n-type material **202**, layer of p-type material **204**, and active layer **206** of the substrate **200** can be epitaxially deposited by known processes. The etch and deposition processes can be controlled by the gases used for each of the etch and deposition processes. For example, the pressure, DC bias, and RF power can be different for the etch and deposition processes, and the times for each of etch and deposition processes can depend on the structure and structure sensitivity to the plasma used during processing. For example, during the etching process and deposition processes, RF power having a frequency of about 162 MHz can be supplied at about 500 W to about 1000 W to ignite a plasma. In some embodiments, RF bias power can be provided at a frequency of about 400 kHz to about 13.56 MHz and can be supplied at about 500 W to about 1000 W to control directionality of the plasma. The RF bias power can be provided in a continuous wave mode or in a pulsed mode. In some embodiments, a pressure within the process chamber can be maintained as about 20 mTorr to about 30 mTorr.

(21) The substrate **200** can be etched using one or more suitable etching processes. For example, the etching process can be a plasma etching process, such as a reactive-ion etch process that uses one or more suitable process gases to form a plasma. In at least some embodiments, the reactive-ion etch process can use a process gases including, but not limited to, at least one of argon (Ar), boron trichloride ($\text{BCl}_{\text{sub.3}}$), chlorine ($\text{Cl}_{\text{sub.2}}$), or hydrogen bromide (HBr), (e.g., a first gas for forming a plasma), as described in greater detail below.

(22) The first layer of material can be etched to any suitable depth. For example, in at least some embodiments, the etching process at **302** can be configured to etch one or more features partially or totally through the first layer of material. In at least some embodiments, the controller **170** can be configured for end-point detection, e.g., to determine which layer of the stack is being etched to modify etching and/or passivation process conditions. For illustrative purposes, the etching process at **302** is configured to etch partially through the layer of p-type material **204** (see FIG. 2A, for example). Additionally, as noted above, a profile and angle of sidewalls **208** formed during **302** can be tuned for a required substrate aspect ratio by adjusting, for example, a gas flow sequencing during **302**.

(23) The reactive-ion etch process at **302** can use one or more suitable etch recipes. For example, one or more of the above process gases (Ar), boron trichloride ($\text{BCl}_{\text{sub.3}}$), chlorine ($\text{Cl}_{\text{sub.2}}$), or hydrogen bromide (HBr) can be supplied at one or more suitable flow rates for a predetermined time. In at least some embodiments, the process gas can be at least one of Ar, $\text{BCl}_{\text{sub.3}}$, $\text{Cl}_{\text{sub.2}}$, or HBr that can be supplied at a flow rate of about 50 sccm to about 200 sccm, which can be supplied for about 3 seconds to about 6 seconds. In at least some embodiments, the process gas at **302** can be supplied in intervals. For example, one or more of Ar, $\text{BCl}_{\text{sub.3}}$, $\text{Cl}_{\text{sub.2}}$, or HBr can be initially supplied at a first flow rate for a first predetermined time and subsequently one or more

of Ar, BCl.sub.3, Cl.sub.2, or HBr can be supplied at a second flow rate for a second predetermined time. The first flow rate and the second flow rate can be the same or different from each other. Likewise, the first predetermined time and the second predetermined time can be the same or different from each other. For example, in one particular embodiment, etching comprises reactive-ion etching including supplying at least one of one BCl.sub.3, Cl.sub.2, or HBr at a flow rate equal to or greater than about 50 sccm for about 3 seconds, and subsequently or simultaneously supplying Ar at a flow rate equal to or greater than about 50 sccm for about 3 seconds. By controlling an RF bias at the substrate, directionality of the BCl.sub.3, Cl.sub.2, or HBr ions can be controlled toward a bottom of the features in the substrate, as shown by the directional arrows in FIGS. 2C-2D.

(24) Next, at **304** and as depicted in FIG. 2B, a protective layer of one or more materials can be deposited over etched (e.g., exposed) sidewalls of the one or more features formed in the first layer of material (e.g., to cover the layer of p-type material **204**). The inventors have found that depositing a protective layer of the one or more materials over the etched sidewalls (e.g., sidewalls **208**) of the layer of p-type material **204** can protect the sidewalls **208** during the etching process. For example, the protective layer can be configured to cover the etched sidewalls of the substrate **200**, thus protecting the etched sidewalls from being exposed to the plasma used during the etching process. In at least some embodiments, the protective layer can be a dielectric layer **210** (e.g., a first dielectric layer). The dielectric materials used to form the dielectric layer **210** can be any suitable dielectric material including carbon, silicon, nitrogen, gallium, oxide, aluminum oxide, and combinations thereof. In at least some embodiments, the dielectric layer **210** can be a carbon film layer, a polymer layer (e.g., linear, branched, crosslinked, or networked), or an oxidation mask layer (e.g., silicon, silicon oxide, silicon nitride, and the like). The dielectric layer **210** can be deposited using one or more suitable deposition processes, such as physical vapor deposition, chemical vapor deposition, or atomic layer deposition. In at least some embodiments, the dielectric layer **210** can be deposited using chemical vapor deposition. The dielectric layer **210** can be deposited to a thickness that provides adequate coverage of the sidewalls **208** (e.g., a thickness to cover the etched sidewalls of the first layer of material and the etched sidewalls of the second layer). The thickness of the dielectric layer can depend on the etch depth of the dielectric layer and can be about few nanometers to few hundred nanometers.

(25) The deposition process at **304** can use one or more suitable deposition recipes (e.g., using one of octafluorocyclobutane (C.sub.4F.sub.8) or oxygen (O.sub.2)). For example, in at least some embodiments, e.g., when **304** includes depositing a carbon film layer, the process gas can be octafluorocyclobutane (or perfluorocyclobutane) (C.sub.4F.sub.8) that can be supplied at a flow rate of about 50 sccm to about 150 sccm, which can be supplied for about 2 seconds to about 5 seconds. In at least some embodiments, such as when **304** includes depositing an oxidation mask, oxygen gas (O.sub.2), along with a silicon precursor and optionally a nitrogen gas can be supplied at a total flow rate of about 50 sccm for about 5 seconds (e.g., to create thin oxide dielectric layers). A thickness of the dielectric layers can depend on one or more factors, such as etch chemistry used, photonic device structure, and/or composition of the n-type material **202**, layer of p-type material **204**, and active layer **206**.

(26) Next, at **306** and as depicted in FIG. 2C, a second layer of material of the substrate can be etched. For example, in at least some embodiments, the second layer of material can be the active layer **206**. Alternatively, the second layer of material can be the n-type material **202**, such as when the active layer **206** is not present. In at least some embodiments, the same etching process used at **302** can be used at **306**. Alternatively, a different etching process can be used at **306**. The etch process at **306** can be achieved using different gases and plasma conditions, such as bias, RF power and pressure, compared to **302**. As noted above, the etching process at **306** can be configured to etch partially or totally through a layer of material. For illustrative purposes, the etching process at **306** is configured to finish etching through the p-type material **204** and totally through the active

layer **206**, thus exposing sidewalls **212** that include the remaining portions of the p-type material **204** and the active layer **206** (see FIG. 2C).

(27) Next, at **308** and as depicted in FIG. 2D, a dielectric layer **214** (e.g., a second dielectric layer) can be deposited over etched sidewalls of the second layer of material, e.g., sidewalls **212** that include the remaining portions of the p-type material **204** and the active layer **206**, in a manner as described above with respect to **304** (see FIG. 2D). In at least some embodiments, the same deposition process used at **304** can be used at **308**. Alternatively, a different deposition process can be used at **308**. For example, in at least some embodiments, the dielectric layer **210** and the dielectric layer **214** can be formed from the same material (e.g., C.sub.4F.sub.8). Alternatively, the dielectric layer **210** and the dielectric layer **214** can be formed from a different material (e.g., the dielectric layer **210** can be a polymer layer formed using C.sub.4F.sub.8 and the dielectric layer **214** can be an oxide layer formed using O.sub.2, or vice versa).

(28) The process continues until a desired depth of etching is reached through the substrate **200**. For example, as illustrated in FIG. 2E the etching process can continue into a third layer of material (e.g., the layer of n-type material **202**), or in some embodiments the etching process can continue to or into the base layer of the substrate **200**. Additionally, after each etching process, a dielectric layer can be deposited to cover the exposed sidewalls of a corresponding layer of material, e.g., **302-308** can be repeated as desired until the desired depth of etching is reached through the substrate **200**.

(29) During **302-308**, the controller **170** can be configured to control one or more of the above-described variables to optimize (e.g., to achieve a balance of sidewall protection and etch depth) the method **300**. For example, the controller **170** can control which type of process gas(es) are used during **302** and **306**. For example, the controller **170** can use BCl.sub.3 gas at **302** and Cl.sub.2 or HBr gas at **306**, and while performing **302** and **306** the controller **170** can vary one or more of the RF/DC power, RF/DC bias, gas flow rate and/or time, and/or process chamber pressure to control an etch depth. Similarly, the controller **170** can control which type of process gas(es) are used during **304** and **308**. For example, while performing **304** and **308** the controller **170** can vary one or more of the RF/DC power, RF/DC bias, gas flow rate and/or time, and/or process chamber pressure to control a deposition thickness. Additionally, in at least some embodiments, a sidewall profile and angle can be tuned for a required substrate aspect ratio by adjusting, for example, a gas flow sequencing during **302-308**. For example, in at least some embodiments, using carbon source or oxygen can dictate the type of deposition created for sidewall protection purposes. The combination of the gas and step time used can modulate the deposition layer thickness.

(30) In at least some embodiments, after the substrate **200** has been etched to a desired depth, the dielectric layers can be removed using one or more conventional removal apparatus and removal processes, e.g., HF dilute wet etching apparatus/process (buffer HF dip). For example, in the illustrated embodiment, after the n-type material has been etched, the dielectric layer **210** and the dielectric layer **214** can be removed from the sidewall **208** and the sidewall **212**, and the substrate **200** can be further processed as needed, e.g., to continue fabrication of structure and/or devices on the substrate **200**.

(31) FIGS. 4A and 4B are diagrams of photonic devices fabricated using the method of FIG. 3 in accordance with at least some embodiments of the present disclosure. For example, FIGS. 4A and 4B illustrate a plurality of circular die **400a** and rectangular die **400b**, respectively. In at least some embodiments, the plurality of circular die **400a** and rectangular die **400b** can be one or more of the above described photonic devices (e.g., an LED, a laser, a photodetector, a solar cell, or the like). For example, in embodiments, the plurality of circular die **400a** and rectangular die **400b** can be a plurality of circular uLEDs and a plurality of rectangular uLEDs, respectively. Each pillar of circular LEDs and rectangular LEDs can comprise a single or multiple light emitting elements. Each pillar of the plurality of circular LEDs and rectangular LEDs can have a die size of sub-micron to about several millimeters (e.g., less than 1 μm to about 10 mm) and a pitch (e.g., a

spacing between the centers of two adjacent pillars) of sub-micron to several hundred microns (e.g., less than 1 μm to about 700 μm). In at least some embodiments, after the pillars of circular LEDs and rectangular LEDs are fabricated using the method 300, each of the pillars, e.g., after singulation, becomes an independent die that can be, for example, transferred onto display backplanes.

(32) While the foregoing is directed to embodiments of the present disclosure, other and further embodiments of the disclosure may be devised without departing from the basic scope thereof.

Claims

1. A method of processing a photonic device, comprising: etching, using a plasma etch process that uses a first gas, a first epitaxial layer of material of the photonic device to form a feature in the first epitaxial layer having etched sidewalls, wherein the photonic device comprises a base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide ($\text{Al}_{\text{x}}\text{In}_{\text{y}}\text{Ga}_{\text{1-x-y}}\text{As}$), aluminum indium gallium phosphide ($\text{Al}_{\text{x}}\text{In}_{\text{y}}\text{Ga}_{\text{1-x-y}}\text{P}$), aluminum indium gallium nitride ($\text{Al}_{\text{x}}\text{In}_{\text{y}}\text{Ga}_{\text{1-x-y}}\text{N}$), aluminum indium gallium arsenide phosphide ($\text{Al}_{\text{x}}\text{In}_{\text{y}}\text{Ga}_{\text{1-x-y}}\text{As}_{\text{z}}\text{P}_{\text{1-z}}$); depositing, using a plasma deposition process that uses a second gas different from the first gas, a first dielectric layer in direct contact with the etched sidewalls of the feature formed in the first epitaxial layer of material to cover the etched sidewalls of the feature formed in the first epitaxial layer of material; exposing a second epitaxial layer of material of the photonic device disposed below the first epitaxial layer by etching, using the first gas, through the first dielectric layer deposited in the feature, to form the etched sidewalls of the feature in the second epitaxial layer to expose the second epitaxial layer of material, wherein at least a portion of the first dielectric layer deposited in contact with the etched sidewalls of the feature formed in the first epitaxial layer of material is present after exposing the second epitaxial layer of material; and depositing, using the second gas, a second dielectric layer in direct contact with the etched sidewalls of the second epitaxial layer of material, wherein the base layer is different from both the first epitaxial layer and the second epitaxial layer in that the base layer is not etched during etching of the first epitaxial layer and the second epitaxial layer.

2. The method of claim 1, wherein etching comprises reactive-ion etching including using at least one of argon (Ar), boron trichloride (BCl_3), chlorine (Cl_2), or hydrogen bromide (HBr), and wherein depositing comprises using one of octafluorocyclobutane (C_4F_8) or oxygen (O_2).

3. The method of claim 1, wherein etching comprises supplying the first gas at a flow rate of about 150 sccm to about 200 sccm for about 3 seconds, and wherein depositing comprises supplying the second gas at a flow rate of about 100 sccm to about 150 sccm for about 2 seconds.

4. The method of claim 1, wherein etching comprises reactive-ion etching including supplying at least one of one BCl_3 , Cl_2 , of HBr at a flow rate equal to or greater than about 50 sccm for about 3 seconds, and one of simultaneously or subsequently supplying Ar at a flow rate equal to or greater than about 50 sccm for about 3 seconds.

5. The method of claim 1, wherein depositing the first dielectric layer and the second dielectric layer comprises depositing at least one of a carbon film layer, a polymer layer, or an oxidation mask layer.

6. The method of claim 1, wherein etching the first epitaxial layer of material and the second epitaxial layer of material comprises etching one of a p-type material, an n-type material, or a multiple quantum well, and wherein the first epitaxial layer of material is different from the second epitaxial layer of material.

7. The method of claim 1, further comprising processing the photonic device to form one of an LED, a laser, a photodetector, or a solar cell.

8. The method of claim 1, further comprising removing at least one of the first dielectric layer or the second dielectric layer after both the first epitaxial layer of material and the second epitaxial layer of material have been etched.
9. The method of claim 1, wherein the first dielectric layer and the second dielectric layer comprises carbon, silicon, nitrogen, gallium, oxygen (O.sub.2), or aluminum oxide and are deposited in contact with the etched sidewalls of the first epitaxial layer of material and the etched sidewalls of the second epitaxial layer of material to cover the etched sidewalls of the first epitaxial layer of material and the etched sidewalls of the second epitaxial layer of material.
10. A non-transitory computer readable storage medium having instructions stored thereon that, when executed by a processor, perform a method of processing a photonic device having one or more epitaxially deposited layers, the method comprising: etching, using a plasma etch process that uses a first gas, a first epitaxial layer of material of the photonic device to form a feature in the first epitaxial layer having etched sidewalls, wherein the photonic device comprises a base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide (Al.sub.xIn.sub.yGa.sub.1-x-yAs), aluminum indium gallium phosphide (Al.sub.xIn.sub.yGa.sub.1-x-yP), aluminum indium gallium nitride (Al.sub.xIn.sub.yGa.sub.1-x-yN), aluminum indium gallium arsenide phosphide (Al.sub.xIn.sub.yGa.sub.1-x-yAs.sub.zP.sub.1-z); depositing, using a plasma deposition process that uses a second gas different from the first gas, a first dielectric layer in direct contact with the etched sidewalls of the feature formed in the first epitaxial layer of material to cover the etched sidewalls of the feature formed in the first epitaxial layer of material; exposing a second epitaxial layer of material of the photonic device disposed below the first epitaxial layer by etching, using the first gas, through the first dielectric layer deposited in the feature, to form the etched sidewalls of the feature in the second epitaxial layer to expose the second epitaxial layer of material, wherein at least a portion of the first dielectric layer deposited in contact with the etched sidewalls of the feature formed in the first epitaxial layer of material is present after exposing the second epitaxial layer of material; and depositing, using the second gas, a second dielectric layer in direct contact with the etched sidewalls of the second epitaxial layer of material, wherein the base layer is different from both the first epitaxial layer and the second epitaxial layer in that the base layer is not etched during etching of the first epitaxial layer and the second epitaxial layer.
11. The non-transitory computer readable storage medium of claim 10, wherein etching comprises reactive-ion etching including using at least one of argon (Ar), boron trichloride (BCl.sub.3), chlorine (Cl.sub.2), or hydrogen bromide (HBr), and wherein depositing comprises using one of octafluorocyclobutane (C.sub.4F.sub.8) or oxygen (O.sub.2).
12. The non-transitory computer readable storage medium of claim 10, wherein etching comprises supplying the first gas at a flow rate of about 150 sccm to about 200 sccm for about 3 seconds, and wherein depositing comprises supplying the second gas at a flow rate of about 100 sccm to about 150 sccm for about 2 seconds.
13. The non-transitory computer readable storage medium of claim 10, wherein etching comprises reactive-ion etching including supplying at least one of one BCl.sub.3, Cl.sub.2, of HBr at a flow rate equal to or greater than about 50 sccm for about 3 seconds, and one of simultaneously or subsequently supplying Ar at a flow rate equal to or greater than about 50 sccm for about 3 seconds.
14. The non-transitory computer readable storage medium of claim 10, wherein depositing the first dielectric layer and the second dielectric layer comprises depositing at least one of a carbon film layer, a polymer layer, or an oxidation mask layer.
15. The non-transitory computer readable storage medium of claim 10, wherein etching the first epitaxial layer of material and the second epitaxial layer of material comprises etching one of a p-type material, an n-type material, or a multiple quantum well, and wherein the first epitaxial layer of material is different from the second epitaxial layer of material.

16. The non-transitory computer readable storage medium of claim 10, wherein etching the first epitaxial layer of material and the second epitaxial layer of material comprises etching one of a p-type material, an n-type material, or a multiple quantum well, and wherein the first epitaxial layer of material is different from the second epitaxial layer of material.
17. The non-transitory computer readable storage medium of claim 10, further comprising processing the photonic device to form one of an LED, a laser, a photodetector, or a solar cell.
18. The non-transitory computer readable storage medium of claim 10, further comprising removing at least one of the first dielectric layer or the second dielectric layer after both the first epitaxial layer of material and the second epitaxial layer of material have been etched.
19. The non-transitory computer readable storage medium of claim 10, wherein the first dielectric layer and the second dielectric layer comprises carbon, oxygen, silicon, nitrogen, gallium, oxide (O.sub.2), or aluminum oxide and are deposited in contact with the etched sidewalls of the first epitaxial layer of material and the etched sidewalls of the second epitaxial layer of material to cover the etched sidewalls of the first epitaxial layer of material and the etched sidewalls of the second epitaxial layer of material.
20. An apparatus for processing a photonic device having one or more epitaxially deposited layers, comprising: a plasma processing chamber configured to: etch, using a first gas, a first epitaxial layer of material and a second epitaxial layer of material of the photonic device, the photonic device to form a feature in the first epitaxial layer having etched sidewalls, wherein the photonic device comprises a base layer comprising at least one of silicon, germanium, sapphire, aluminum indium gallium arsenide (Al.sub.xIn.sub.yGa.sub.1-x-yAs), aluminum indium gallium phosphide (Al.sub.xIn.sub.yGa.sub.1-x-yP), aluminum indium gallium nitride (Al.sub.xIn.sub.yGa.sub.1-x-yN), aluminum indium gallium arsenide phosphide (Al.sub.xIn.sub.yGa.sub.1-x-yAs.sub.zP.sub.1-z); deposit, using a plasma deposition process that uses a second gas different from the first gas, a first dielectric layer in direct contact with the etched sidewalls of the first epitaxial layer of material to cover the etched sidewalls of the feature formed in the first epitaxial layer of material; expose the second epitaxial layer of material of the photonic device disposed below the first epitaxial layer by etching, using the first gas, through the first dielectric layer deposited in the feature, to form the etched sidewalls of the feature in the second epitaxial layer to expose the second epitaxial layer of material, wherein at least a portion of the first dielectric layer deposited in contact with the etched sidewalls of the feature formed in the first epitaxial layer of material is present after exposing the second epitaxial layer of material; and deposit using the second gas, a second dielectric layer in direct contact with the etched sidewalls of the second epitaxial layer of material, wherein the base layer is different from both the first epitaxial layer and the second epitaxial layer in that the base layer is not etched during etching of the first epitaxial layer and the second epitaxial layer.
-