

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250273592

Kind Code

A1

Publication Date

August 28, 2025

Inventor(s)

JUNG; JinHee et al.

PARTIALLY SHIELDED SEMICONDUCTOR DEVICE AND METHOD FOR FORMING THE SAME

Abstract

A partially shielded semiconductor device and a method for forming the same are provided. The method includes: providing a semiconductor package; dispensing an ink composition to form a barrier structure on a surface of the semiconductor package, wherein the barrier structure divides the surface of the semiconductor package into at least a first portion and a second portion; dispensing a fluid including a metal precursor onto the first portion of the surface of the semiconductor package, wherein the barrier structure prevents the fluid flowing to the second portion of the surface of the semiconductor package; and curing the fluid to form an electromagnetic interference (EMI) shield.

Inventors: JUNG; JinHee (Incheon, KR), KIM; ChangOh (Incheon, KR), KIM; WooSoon (Incheon, KR)

Applicant: STATS ChipPAC Pte. Ltd. (Singapore, SG)

Family ID: 1000008460535

Appl. No.: 19/055522

Filed: February 18, 2025

Foreign Application Priority Data

CN

202410197630.6

Feb. 22, 2024

Publication Classification

Int. Cl.: H01L23/552 (20060101); H01L21/56 (20060101); H01L23/26 (20060101); H01L23/31 (20060101); H01L25/18 (20230101)

U.S. Cl.:

Background/Summary

TECHNICAL FIELD

[0001] The present application generally relates to semiconductor technology, and more particularly, to a partially shielded semiconductor device and a method for forming the same.

BACKGROUND OF THE INVENTION

[0002] The semiconductor industry is constantly faced with complex integration challenges as consumers want their electronics to be smaller, faster and higher performance with more and more functionalities packed into a single device. Recently, millimeter Wave (mmWave) modules are introduced for the fifth-generation (5G) communication technology, and most of them may be partially covered by an electromagnetic interference (EMI) shield because the other region of the mmWave modules may be left uncovered for antennas or for other purposes. However, the conventional method for forming a partially shielded semiconductor device is complex, resulting in excess cost and low reliability.

[0003] Therefore, a need exists for a partially shielded semiconductor device with reduced cost.

SUMMARY OF THE INVENTION

[0004] An objective of the present application is to provide a semiconductor device with low cost and/or improved reliability.

[0005] According to an aspect of the present application, a method for forming a partially shielded semiconductor device is provided. The method may include: providing a semiconductor package; dispensing an ink composition to form a barrier structure on a surface of the semiconductor package, wherein the barrier structure divides the surface of the semiconductor package into at least a first portion and a second portion; and dispensing a fluid including a metal precursor onto the first portion of the surface of the semiconductor package, wherein the barrier structure prevents the fluid flowing to the second portion of the surface of the semiconductor package; and curing the fluid to form an electromagnetic interference (EMI) shield.

[0006] According to another aspect of the present application, a partially shielded semiconductor device is provided. The partially shielded semiconductor device may include: a semiconductor package; a barrier structure formed on a surface of the semiconductor package, wherein the barrier structure is made of an ink composition and divides the surface of the semiconductor package into at least a first portion and a second portion; and an electromagnetic interference (EMI) shield formed on the first portion of the surface of the semiconductor package but not on the second portion of the surface of the semiconductor package, wherein the EMI shield is made of a fluid including a metal precursor.

[0007] It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only, and are not restrictive of the invention. Further, the accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description, serve to explain principles of the invention.

Description

BRIEF DESCRIPTION OF DRAWINGS

[0008] The drawings referenced herein form a part of the specification. Features shown in the

drawing illustrate only some embodiments of the application, and not of all embodiments of the application, unless the detailed description explicitly indicates otherwise, and readers of the specification should not make implications to the contrary.

[0009] FIG. 1 is a cross-sectional view illustrating a partially shielded semiconductor device.

[0010] FIGS. 2A to 2E are cross-sectional views illustrating various steps of a method for forming a barrier structure with an ink composition according to an embodiment of the present application.

[0011] FIGS. 3A to 3E are perspective views illustrating various steps of a method for forming a barrier structure with an ink composition according to an embodiment of the present application.

[0012] FIGS. 4A to 4D are cross-sectional views illustrating various steps of a method for forming a partially shielded semiconductor device according to an embodiment of the present application.

[0013] FIG. 5 is a cross-sectional view illustrating a partially shielded semiconductor device according to an embodiment of the present application.

[0014] FIG. 6 is a cross-sectional view illustrating a partially shielded semiconductor device according to another embodiment of the present application.

[0015] FIG. 7 is a cross-sectional view illustrating a partially shielded semiconductor device according to another embodiment of the present application.

[0016] The same reference numbers will be used throughout the drawings to refer to the same or like parts.

DETAILED DESCRIPTION OF THE INVENTION

[0017] The following detailed description of exemplary embodiments of the application refers to the accompanying drawings that form a part of the description. The drawings illustrate specific exemplary embodiments in which the application may be practiced. The detailed description, including the drawings, describes these embodiments in sufficient detail to enable those skilled in the art to practice the application. Those skilled in the art may further utilize other embodiments of the application, and make logical, mechanical, and other changes without departing from the spirit or scope of the application. Readers of the following detailed description should, therefore, not interpret the description in a limiting sense, and only the appended claims define the scope of the embodiment of the application.

[0018] In this application, the use of the singular includes the plural unless specifically stated otherwise. In this application, the use of “or” means “and/or” unless stated otherwise. Furthermore, the use of the term “including” as well as other forms such as “includes” and “included” is not limiting. In addition, terms such as “element” or “component” encompass both elements and components including one unit, and elements and components that include more than one subunit, unless specifically stated otherwise. Additionally, the section headings used herein are for organizational purposes only, and are not to be construed as limiting the subject matter described.

[0019] As used herein, spatially relative terms, such as “beneath”, “below”, “above”, “over”, “on”, “upper”, “lower”, “left”, “right”, “vertical”, “horizontal”, “side” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. It should be understood that when an element is referred to as being “connected to” or “coupled to” another element, it may be directly connected to or coupled to the other element, or intervening elements may be present.

[0020] FIG. 1 illustrates a cross-sectional view of a partially shielded semiconductor device **100**. The device **100** may include a substrate **110**, a plurality of electronic components **122**, **124** and **126** mounted on the substrate **110**, and an encapsulant **130** covering the electronic components **122**, **124** and **126**. As the plurality of electronic components **122**, **124** and **126** may have different functions, electromagnetic interferences may exist between the electronic components **122**, **124** and **126**,

which may be desired to be removed or reduced. Furthermore, electromagnetic interferences from the exterior environment may also be desired to be removed or reduced for some or all of the electronic components **122**, **124** and **126** or the other components mounted on the substrate **110** such as passive components (e.g., inductors, capacitors). As an example, an EMI shield **140** may be formed to cover the electronic components **124** and **126** that are susceptible to or generate EMI, radio frequency interference (RFI), harmonic distortion, or inter-device interferences. The EMI shield **140** may for example be composed substantially of metal material(s). In this example, the EMI shield **140** may include a first portion **142** filled in a trench of the encapsulant **130**, and a second portion **144** covering an outer surface of the encapsulant **130**. It can be appreciated that the EMI shield **140** may take any other suitable shapes and forms depending on the requirement of EMI reduction.

[0021] In a conventional method to form the EMI shield **140**, a trench is first formed in the encapsulant **130**, and then the trench is filled with a conductive material such as copper or aluminum to form the first portion **142** of the EMI shield **140**. Afterwards, a masking tape is adhered on an area of the encapsulant **130** where the EMI shield is not needed, and a sputtering method or other similar vapor deposition method is employed to deposit the conductive material onto the encapsulant **130**, as well as onto the masking tape. At last, the masking tape is stripped to remove the conductive material deposited thereon, i.e., the area covered by the masking tape can be uncovered by the conductive material, and the left part of the conductive material forms the second portion **144** of the EMI shield **140**. As can be seen, the above method is complex, resulting in excess cost and low reliability.

[0022] To address at least one of the above problems, a method for making a partially shielded semiconductor device is provided in an aspect of the present application. In the method, an ink composition is dispensed on a surface of a semiconductor package to form a barrier structure. The barrier structure may divide the surface of the package into at least a first portion and a second portion, and when a fluid including a metal precursor or similar materials is dispensed onto the first portion of the surface of the package, the barrier structure can prevent the fluid from flowing across it to the second portion of the surface of the package. Accordingly, the second portion of the surface of the package may not be covered by the fluid including the metal precursor. Then, the fluid may be cured to form an EMI shield partially covering the semiconductor package.

[0023] Referring to FIGS. 2A to 2E and FIGS. 3A to 3E, various steps of a method for forming a barrier structure with an ink composition are illustrated according to an embodiment of the present application. FIGS. 2A to 2E are cross-sectional views illustrating various steps of the method, and FIGS. 3A to 3E are corresponding perspective views of the steps. In the following, the method will be described with reference to FIGS. 2A to 2E and FIGS. 3A to 3E in more details.

[0024] Referring to FIG. 2A, an inkjet apparatus **300** is provided. The inkjet apparatus **300** may at least include a dispensing nozzle **310** configured for dispensing an ink composition and a light source **320** configured for irradiating a light beam with a predetermined intensity.

[0025] In some embodiments, the ink composition may include a photocurable material and a thermosetting material. The photocurable material may include a curable compound having a (meth) acryloyl group, a curable compound having a vinyl group, a curable compound having a maleimide group, or other suitable materials. The thermosetting material may include an organic acid, an amine compound, an amide compound, a hydrazide compound, an imidazole compound, an imidazoline compound, a phenol compound, a urea compound, a polysulfide compound, an acid anhydride, or other suitable materials. For example, the ink composition may be Sekisui 3D inkjet materials commercially available from SEKISUI CHEMICAL CO., LTD. However, the present application is not limited to the above examples. In some other embodiments, the ink composition may only include a photocurable material or a thermosetting material.

[0026] Referring to FIGS. 2A and 3A, a substrate **210** is provided, and the dispensing nozzle **310** of the inkjet apparatus **300** is controlled to produce droplets **311** of the ink composition in the order of

several to several tens of micrometers (for example, 20 μm) in diameter, which will be projected towards the substrate **210**. The substrate **210** may include a semiconductor package, a semiconductor wafer, a semiconductor wafer after dicing, a printed circuit board or any other support member for mounting a semiconductor element. By moving the substrate **210** or the dispensing nozzle **310** relative to each other, the droplets **311** can be dispensed onto a surface of the substrate **210** at a location where the barrier structure is to be formed.

[0027] Referring to FIGS. 2B and 3B, the substrate **210** is moved until the droplets **311** dispensed onto the substrate **210** in FIG. 2A are right below the light source **320** and thus can be irradiated by a light beam from the light source **320**. Alternatively, the light source **320** of the inkjet apparatus **300** may be moved to a position right above the droplets **311**. Then, the light source **320** is controlled to irradiate a light beam **321** such as ultraviolet (UV) light with a predetermined intensity (for example, $>5000 \text{ mW/cm}^2$), which can be used to cure the material in the droplets **311**. After the droplets **311** are cured by the light beam **321** and solidify, a first barrier structure **251** is formed on the surface of the substrate **210**. In a specific example, each cured droplet **311** may have a spherical shape with a width of 50 μm and a height of 5 μm . It should be noted that while the light source **320** is controlled to cure the droplets **311** dispensed, the dispensing nozzle **310** continues to dispense more droplets **311** onto other positions of the surface of the substrate **210**. Since the light source **320** and the dispensing nozzle **310** move simultaneously relative to the substrate **210**, the time the dispensing nozzle **310** stays above a position over the substrate **210** for liquid dispensing should be sufficient for the time for UV curing, otherwise the liquid droplets **311** may not be able to be cured well.

[0028] Referring to FIGS. 2C and 3C, the substrate **210** is moved until the droplets **311** dispensed in FIG. 2B (i.e., a portion of the droplets **311** different from but adjacent to the droplets **311** dispensing in FIG. 2A) are right below the light source **320**, and the light source **320** is controlled to cure the droplets **311** dispensing in FIG. 2B. By continuously moving the substrate **210** relative to the dispensing nozzle **310**, dispensing the droplets **311** of the ink composition and curing the droplets **311** with light irradiation, the first barrier structure **251** can be formed on the substrate **210**, for example, across a width of the substrate **210**. As the inkjet apparatus **300** can accurately control the position and/or the dispensing time of the droplets **311**, the first barrier structure **251** can be directly formed at a desired area with a desired shape without any mask, or any photolithography process.

[0029] Referring to FIGS. 2D and 2E and FIGS. 3D and 3E, a second barrier structure **252** is formed on the first barrier structure **251** which has been cured and solidified to obtain a barrier structure **250** with a desired height. The second barrier structure **252** may be formed using a process similar as that described with reference to FIGS. 2A to 2C and FIGS. 3A to 3C, and will not be elaborated herein. It can be appreciated that the second barrier structure **252** may have the same layout as the first barrier structure **251** or a different layout from the first barrier structure **251**. In some other embodiments, more layers of barrier structures may be formed using the process similar as that shown in FIGS. 2A to 2C and FIGS. 3A to 3C to obtain a stack of barrier structures with a desired height.

[0030] In some embodiments, when the ink composition includes a thermosetting material, the barrier structure **250** may be cured under a predetermined temperature for a predetermined period (for example, under 170° C. for 1 hour) which depends on properties of the thermosetting material.

[0031] In the above embodiment, an inkjet system is used to form the barrier structure **250**.

However, the present application is not limited thereto. In some other embodiments, the barrier structure **250** may be formed by an aerosol jetting system, an electrohydrodynamic (EHD) jetting system, or other directly dispensing systems.

[0032] Referring to FIGS. 4A to 4D, various steps of a method for forming a partially shielded semiconductor device are illustrated according to an embodiment of the present application. In the following, the method will be described with reference to FIGS. 4A to 4D in more details.

[0033] Referring to FIG. 4A, a semiconductor package **401** is provided. Specifically, the semiconductor package **401** may include a substrate **410** that provides support and connectivity for electrical components and devices. By way of example, the substrate **410** may include a printed circuit board (PCB), a carrier substrate, a semiconductor substrate with electrical interconnections, a ceramic substrate, a laminate interposer, a strip interposer, a leadframe, or other suitable substrates. The substrate **410** may include any structure on or in which an integrated circuit system can be fabricated. In the example shown in FIG. 4A, the substrate **410** includes redistribution structures **412** having one or more dielectric layers and one or more conductive layers between and through dielectric layers. The conductive layers may define pads, traces and plugs through which electrical signals or voltages can be distributed horizontally and vertically across the redistribution structures **412**. It could be appreciated that, the redistribution structures **412** may be implemented in various structures and types, but aspects of the present application are not limited to the above example.

[0034] As shown in FIG. 4A, a plurality of electronic components **422**, **424** and **426** may be mounted on a top surface of the substrate **410**. The electronic components **422**, **424** and **426** may include any of a variety of types of semiconductor dice, semiconductor packages, or discrete devices. For example, the electronic components **422**, **424** and **426** may include a digital signal processor (DSP), a microcontroller, a microprocessor, a network processor, a power management processor, an audio processor, a video processor, an RF circuit, a wireless baseband system-on-chip (SoC) processor, a sensor, a memory controller, a memory device, an application specific integrated circuit, etc. An encapsulant **430** is formed on the top surface of the substrate **410** and encapsulates the electronic components **422**, **424** and **426**. The encapsulant **430** may be made of polymer composite material, such as epoxy resin with filler, epoxy acrylate with filler, or polymer with proper filler, but the scope of this application is not limited thereto.

[0035] By way of example, the first electronic component **422** and the second electronic components **424** and **426** may have different functions, and electromagnetic interferences may exist between the electronic components **422**, **424** and **426**. Accordingly, an EMI shield may be formed in subsequent steps to cover the second electronic components **424** and **426** that are susceptible to or generate EMI.

[0036] Referring to FIG. 4B, a trench **432** is formed in the encapsulant **430** and between the first electronic component **422** and the second electronic components **424** and **426**. The trench **432** may expose the substrate **410**, and optionally a conductive pad of the redistribution structures **412**.

[0037] In some embodiments, a laser ablation process may be employed to form the trench **432** in the encapsulant **430**. The laser ablation process can be controlled by computer-aided design data, and therefore the size and depth of the trench **432** can be accurately controlled. In some other embodiments, the trench **432** may be formed by an etching process, or any other process known in the art so long as the encapsulant material can be partially removed as desired.

[0038] Referring to FIG. 4C, an ink composition is dispensed to form one or more barrier structures **450** on the top surface of the encapsulant **430**. The barrier structures **450** divide the top surface of the encapsulant **430** into at least a first portion I and a second portion II. In a subsequent step, the EMI shield will be formed on the first portion I of the top surface of the encapsulant **430** but not on the second portion II of the top surface of the encapsulant **430**.

[0039] The method for forming the barrier structures **450** may refer to the embodiments described with reference to FIGS. 2A to 2E and FIGS. 3A to 3E, and will not be elaborated herein. It can be understood that the barrier structures **450** shown in FIG. 4C are only examples. In some other embodiments, the barrier structures **450** may take other shapes (for example, a line, a ring shape, a rectangular shape, etc.) and have different heights.

[0040] Referring to FIG. 4D, a fluid including a metal precursor is dispensed onto the first portion I of the top surface of the encapsulant **430**. In some embodiments, the metal precursor may include metal cations or metal particles such as silver, copper or gold. After the fluid is dispensed on the

first portion I of the top surface of the encapsulant **430**, the barrier structures **450** can prevent the fluid from flowing across them to the second portion II of the top surface of the encapsulant **430** as each barrier structure **450** may be higher (for example, 5 to 15 μm or even higher) than the fluid. Afterwards, the fluid may be cured to form an EMI shield **440**.

[0041] In the example shown in FIG. **4D**, an aerosol jetting system **480** may be used to dispense the fluid on the first portion I of the top surface of the encapsulant **430**. The aerosol jetting system **480** can atomize the fluid via ultrasonic or pneumatic means, so as to produce droplets **481** in the order of one or more micrometers in diameter but generally less than ten micrometers in diameter. The droplets **481** may be entrained in a gas stream and delivered to a print head. At the print head, a sheath gas flow (for example, N.sub.2 gas flow) may be introduced to focus the droplets **481** in a tightly collimated beam of material. Then, the combined gas streams may fly out of the print head through a converging nozzle that compresses the aerosol stream to a small diameter. Then, the jet of droplets **481** may fly out of the print head at a high velocity and impinge upon the first portion I of the top surface of the encapsulant **430**. Thus, the fluid (i.e., droplets **481**) can cover the first portion I of the top surface of the encapsulant **430** by moving the substrate **410** relative to the aerosol jetting system **480** (for example, along the x-axis direction and/or the y-axis direction shown in FIG. **4C**) and continuously dispensing the droplets **481**. Then, the fluid may be cured by light irradiation and/or heating to form the EMI shield **440**, depending on properties of the fluid and the metal precursor.

[0042] In the above example, an aerosol jetting system **480** is used to form the EMI shield **440**. However, the present application is not limited thereto. In some other embodiments, the EMI shield **440** may be formed by a spray system, an inkjet system, or other dispensing systems. In some embodiments, the EMI shield **440** may be formed by multiple dispensing techniques. For example, a spray system may be used to dispense the fluid including the metal precursor onto a region with a larger area (for example, the right part of the first portion I of the top surface of the encapsulant **430**), while an inkjet system or an aerosol jetting system may be used to dispense the fluid onto a region with a smaller area (for example, the left part of the first portion I of the top surface of the encapsulant **430**), so as to increase production capacity.

[0043] In some embodiments, when dispensing the fluid including the metal precursor, the substrate **410** can be moved, for example, along the z-axis direction shown in FIG. **4D**, to adjust a distance between the encapsulant **430** and the nozzle of the dispensing system **480**. Accordingly, as shown in FIG. **4D**, the fluid including the metal precursor can be dispensed into the trench **432** and onto lateral surfaces of the encapsulant **430** and the substrate **410**. Thus, after the fluid is cured, the EMI shield **440** may accommodate the second electronic components **424** and **426** thereunder, and be formed in desired positions adjacent to the first electronic components **422**.

[0044] Compared with the EMI shield **140** shown in FIG. **1**, the EMI shield **440** formed by the method described with reference to FIGS. **4A-4D** has multiple shielding areas, but can be formed by reduced processes. Thus, the cost for fabricating the partially shielded semiconductor device is reduced, and the reliability is improved.

[0045] According to another aspect of the present application, a partially shielded semiconductor device is provided.

[0046] Referring to FIG. **5**, a cross-sectional view of a partially shielded semiconductor device **500** is illustrated according to an embodiment of the present disclosure. The partially shielded semiconductor device **500** may include a semiconductor package, a plurality of barrier structures **550**, and an electromagnetic interference (EMI) shield **540**. For example, the semiconductor package may include a substrate **510**, a first electronic component **522** and multiple second electronic components **524** and **526** mounted on the substrate **510**, and an encapsulant **530** formed on the substrate **510** and encapsulating the first electronic component **522** and the second electronic components **524** and **526**. The barrier structures **550** are formed on a top surface of the encapsulant **530**. The barrier structure **550** are made of an ink composition and divide the top surface of the

encapsulant **530** into at least a first portion I and a second portion II. The EMI shield **540** is formed on the first portion I of the top surface of the encapsulant **530** but not on the second portion II of the top surface of the encapsulant **530**. The EMI shield **540** is made of a fluid including a metal precursor.

[0047] In some embodiments, the ink composition may include a photocurable material and/or a thermosetting material.

[0048] In some embodiments, a height of the barrier structure **550** is larger than a thickness of the EMI shield **540**.

[0049] In some embodiments, a trench is formed in the encapsulant **530** and between the first electronic component **522** and the second electronic components **524** and **526**. The EMI shield **540** may fill the trench in the encapsulant **530**.

[0050] The partially shielded semiconductor device **500** can be formed by the steps illustrated in FIGS. **4A** to **4D**. Thus, more details about the partially shielded semiconductor device **500** may refer to the above method embodiments, and will not be elaborated herein.

[0051] In the partially shielded semiconductor device **500** shown in FIG. **5**, the second electronic components **524** and **526** is accommodated by the EMI shield **540**. However, the present application is not limited thereto. In some other embodiments, there may be more shielded areas in the semiconductor devices. Referring to FIG. **6**, by adjusting the configurations of barrier structures **650** and an EMI shield **640**, two first electronic components **621** and **622** are not covered by the EMI shield **640**, two second electronic components **624** and **626** are accommodated by a chamber of the EMI shield **640**, and a third electronic component **628** is accommodated by another chamber of the EMI shield **640**. Further, Referring to FIG. **7** which shows a partially shielded device according to another embodiment of the present application, by adjusting the configurations of barrier structures **750** and a EMI shield **740**, a first electronic component **722** is not covered by the EMI shield **740**, two second electronic components **724** and **726** are accommodated by a first chamber of the EMI shield **740**, a third electronic component **728** is accommodated by a second chamber of the EMI shield **740**, and a fourth electronic component **729** is accommodated by a third chamber of the EMI shield **740**,.

[0052] While the partially shielded semiconductor device of the present application is described in conjunction with corresponding figures, it will be understood by those skilled in the art that modifications and adaptations to the partially shielded semiconductor device may be made without departing from the scope of the present invention.

[0053] The discussion herein included numerous illustrative figures that showed various portions of a partially shielded semiconductor device and a method for making the same. For illustrative clarity, such figures did not show all aspects of each example device. Any of the example devices and/or methods provided herein may share any or all characteristics with any or all other devices and/or methods provided herein.

[0054] Various embodiments have been described herein with reference to the accompanying drawings. It will, however, be evident that various modifications and changes may be made thereto, and additional embodiments may be implemented, without departing from the broader scope of the invention as set forth in the claims that follow. Further, other embodiments will be apparent to those skilled in the art from consideration of the specification and practice of one or more embodiments of the invention disclosed herein. It is intended, therefore, that this application and the examples herein be considered as exemplary only, with a true scope and spirit of the invention being indicated by the following listing of exemplary claims.

Claims

1. A method for forming a partially shielded semiconductor device, comprising: providing a semiconductor package; dispensing an ink composition to form a barrier structure on a surface of

- the semiconductor package, wherein the barrier structure divides the surface of the semiconductor package into at least a first portion and a second portion; dispensing a fluid comprising a metal precursor onto the first portion of the surface of the semiconductor package, wherein the barrier structure prevents the fluid flowing to the second portion of the surface of the semiconductor package; and curing the fluid to form an electromagnetic interference (EMI) shield.
2. The method of claim 1, wherein the ink composition comprises a photocurable material and/or a thermosetting material.
 3. The method of claim 2, wherein dispensing the ink composition to form the barrier structure on the surface of the semiconductor package comprises: dispensing the ink composition on the surface of the semiconductor package; and curing the ink composition by light irradiation and/or heating to form the barrier structure.
 4. The method of claim 1, wherein dispensing the ink composition to form the barrier structure on the surface of the semiconductor package comprises: dispensing the ink composition by using an inkjet system or an aerosol jetting system.
 5. The method of claim 1, wherein dispensing the fluid comprising the metal precursor onto the first portion of the surface of the semiconductor package comprises: dispensing the fluid comprising the metal precursor by using a spray system, an inkjet system, or an aerosol system.
 6. The method of claim 5, wherein dispensing the fluid comprising the metal precursor onto the first portion of the surface of the semiconductor package further comprises: moving the semiconductor package to adjust a distance between the semiconductor package and a nozzle dispensing the fluid.
 7. The method of claim 1, wherein a height of the barrier structure is larger than a thickness of the fluid dispensed on the first portion of the surface of the semiconductor package.
 8. The method of claim 1, wherein the semiconductor package comprises: a substrate; a first electronic component and a second electronic component mounted on the substrate; and an encapsulant formed on the substrate and encapsulating the first electronic component and the second electronic component, wherein the surface of the semiconductor package comprises a top surface of the encapsulant.
 9. The method of claim 8, further comprising: forming a trench in the encapsulant and between the first electronic component and the second electronic component.
 10. The method of claim 9, wherein dispensing the fluid comprising the metal precursor onto the first portion of the surface of the semiconductor package comprising: dispensing the fluid comprising the metal precursor into the trench.
 11. A partially shielded semiconductor device, comprising: a semiconductor package; a barrier structure formed on a surface of the semiconductor package, wherein the barrier structure is made of an ink composition and divides the surface of the semiconductor package into at least a first portion and a second portion; and an electromagnetic interference (EMI) shield formed on the first portion of the surface of the semiconductor package but not on the second portion of the surface of the semiconductor package, wherein the EMI shield is made of a fluid comprising a metal precursor.
 12. The partially shielded semiconductor device of claim 11, wherein the ink composition comprises a photocurable material and/or a thermosetting material.
 13. The partially shielded semiconductor device of claim 11, wherein a height of the barrier structure is larger than a thickness of the EMI shield.
 14. The partially shielded semiconductor device of claim 11, wherein the semiconductor package comprises: a substrate; a first electronic component and a second electronic component mounted on the substrate; and an encapsulant formed on the substrate and encapsulating the first electronic component and the second electronic component, wherein the surface of the semiconductor package comprises a top surface of the encapsulant.
 15. The partially shielded semiconductor device of claim 14, further comprising: a trench formed in

the encapsulant and between the first electronic component and the second electronic component.

16. The partially shielded semiconductor device of claim 15, wherein the EMI shield fills the trench in the encapsulant.
