

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287762

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

SONG; Juneo et al.

VERTICALLY STACKED MICRO DISPLAY PANEL IN WHICH COLOR FILTER IS UNNECESSARY, AND MANUFACTURING METHOD THEREFOR

Abstract

The present invention relates to a vertically stacked LEDoS micro display panel and a manufacturing method therefor, in which an engineering monolithic epitaxy wafer is used when bonding a front wafer and a back wafer to each other, thus making a process for aligning an LED laminate with a CMOS electrode pad unnecessary, and at the same time, each LED laminate emits only light of a specific color, thus making a color filter unnecessary.

Inventors: SONG; Juneo (Suwon-si, KR), MOON; Ji Hyung (Gunpo-si, KR)

Applicant: WAVE LORD CO., LTD (Hwaseong-si, KR)

Family ID: 90472355

Assignee: WAVE LORD CO., LTD (Hwaseong-si, KR)

Appl. No.: 18/860665

Filed (or PCT Filed): March 12, 2024

PCT No.: PCT/KR2024/003153

Foreign Application Priority Data

KR 10-2023-0032710 Mar. 13, 2023

KR 10-2023-0110617 Aug. 23, 2023

Publication Classification

Int. Cl.: H10H29/85 (20250101); H01L25/075 (20060101); H10H20/01 (20250101);
H10H20/813 (20250101); H10H29/01 (20250101); H10H29/80 (20250101);
H10H29/855 (20250101)

CPC **H10H29/857** (20250101); **H01L25/0753** (20130101); **H10H20/017** (20250101);
H10H20/8131 (20250101); **H10H29/032** (20250101); **H10H29/0363** (20250101);
H10H29/0364 (20250101); **H10H29/8323** (20250101); **H10H29/8552** (20250101);

Background/Summary

TECHNICAL FIELD

[0001] The present invention relates to a vertically stacked microdisplay panel that does not require a color filter, and a method of manufacturing the same, and more specifically, to a vertically stacked light-emitting diode-on-silicon (LEDoS) microdisplay panel which eliminates the need for a process of arranging a light-emitting diode (LED) stack and a complementary metal oxide semiconductor (CMOS) electrode pad by using an engineering monolithic epitaxy wafer when a front wafer and a back wafer are bonded and simultaneously eliminates the need for a color filter due to each LED stack being able to emit only light of a specific color, and a method of manufacturing the same.

BACKGROUND ART

[0002] The types of implementation of the metaverse, which has recently been attracting attention, are classified into four types of virtual reality (VR), augmented reality (AR), mixed reality (MR), and extended reality (XR). Among these, it is expected that a metaverse ecosystem will be developed in the future centered on XR that is a reality in which VR, AR and MR are combined. In order to effectively implement XR, there is a need for devices (for example, smart glasses or head-mounted displays) that include microdisplays with a diagonal length of less than 1 inch as a core component, along with software for next-generation computing platforms that can provide innovative user experiences. In particular, the development of high-performance microdisplay panel technologies is absolutely required to provide the greatest immersion, visibility, and convenience to XR users and minimize dizziness.

[0003] As illustrated in FIG. 1, a microdisplay panel **10** of the related art is a technology in which a Si complementary metal oxide semiconductor (CMOS) semiconductor wafer process is combined with a high-resolution, high-luminance, and ultra-small display process. The microdisplay panel **10** of the related art may have a structure in which a Si CMOS wafer **11**, which has a size of 4" or more and a (100) crystal plane and includes a plurality of CMOS electrode pads **12**, is bonded to a transparent wafer **13**, which has a size of less than 4" and includes a micro-light-emitting diode (LED) electrode pad **14** and a plurality of micro-LED chips **15**, through a conductive bonding portion **16**. Meanwhile, the types of microdisplay panels expected to be applied to XR devices include liquid crystal (LC)-based LC on Si (LCoS) panels, organic light-emitting diode (OLED)-based OLED on Si (OLEDoS) panels, and ultra-small micro-LED-based LED on Si (LEDoS) panels with a pixel size of less than 5 μm . VR devices to which low-pixel density displays are applied are being developed and mass-produced around LCOS and OLEDoS panels.

[0004] However, with the development of metaverse implementation technologies, there is an increasing need for lightweight AR, MR, and XR devices to which high-pixel density microdisplay panels are applied. In order to satisfy this need, there is an urgent need to develop an LEDoS technology which is considered to be an ideal solution in theory based on the superior properties of inorganic materials, but a microdisplay panel platform therefor has not yet been established.

[0005] LEDoS based on ultra-small micro-LEDs with a pixel size of less than 5 μm has advantages of an excellent power-to-performance ratio and a short response speed when applied to XR devices and has advantages in that inorganic materials are used to have a long lifespan, power is efficiently

used to reduce heat generation, and a battery is usable for the long term. In particular, since XR devices have a very short distance between a display and the eyes, even a little time delay in image conversion may easily cause discomfort such as dizziness. Therefore, LEDoS which has a nanosecond response speed is considered to be the most suitable for XR devices as compared to LCoS and OLEDoS which have a microsecond response speed.

[0006] Furthermore, it is evaluated that the biggest reason why LEDoS is attracting attention in AR, MR, and XR devices unlike in VR is due to luminance and luminous efficiency. Due to the characteristics of smart glasses that can be worn regardless of location, high brightness is an essential condition for normal operation even in outdoor environments such as sunlight, and in theory, micro-LEDs supports a luminance of tens to millions of nits, and while OLEDs are organic, micro-LEDs are inorganic and thus also have an advantage of high luminous efficiency.

[0007] However, despite the above-described advantages, the biggest reason why LEDoS based on ultra-small micro-LEDs with a pixel size of less than 5 μm are not used as a major component of XR devices is that LEDoS is difficult to mass-produce. That is, in LEDoS, since millions of ultra-small micro-LEDs should be fixed onto a Si CMOS wafer, the process difficulty is high and the yield is very low, which leads to an increase in manufacturing costs to generate a high component price. Thus, the high component price is reflected in the final consumer price, and the LEDoS is supplied as a high-priced XR device, which makes it difficult to meet market demand.

[0008] Meanwhile, as shown in FIG. 2, up to now, LEDoS using a Group III-V compound (GaN, GaP, or the like) micro-LED light source has been developed through traditional approaches such as {circle around (1)} monolithic integration of a wafer (or a unit die) consisting of micro-LED arrays on a Si CMOS wafer or {circle around (2)} hybridization between wafers (or unit dies) on a blue, green, or red light source wafer (or a unit die) on which Si CMOS wafers or micro-LED arrays are manufactured.

[0009] Up to now, one of the biggest obstacles to the development of LEDoS using blue, green, and red micro-LED light sources consisting of Group III-V compounds is that it is not easy to secure a solution for pixels having a size of less than 5 μm . Recently, 5 μm level pixels have been successfully demonstrated using monolithic integration technologies, and some product demonstrations developed based on hybridization technologies have been manufactured using sapphire flip chips to achieve 10 μm level pixels. In addition, it has been demonstrated that it is possible to reduce pixels on a 5 μm level in the same way by using micro tube interconnections in hybridization technologies. However, both monolithic integration and hybridization technologies are impractical solutions with significant difficulties in mass production in terms of quality and yield and have a problem in that mass production is difficult.

[0010] The above-described monolithic integration technology and hybrid technology have the common characteristics in which a front plane wafer consisting of Group III-V compound micro-LED arrays and a Si CMOS back plane wafer consisting of a number of IC electrode pad arrays are each separately designed and manufactured and then assembled. Since micro-LED arrays manufactured at unit die-level or wafer-level on Si CMOS wafers should be arranged ultra-finely in any way, in this case, the arrangement is limited by the precision of a process-related device, which seriously affects pixels and pixel to pixel distance (pitch) limitations and causes a problem that mass production is also difficult. Accordingly, in order to manufacture LEDoS to which blue, green, and red micro-LED light sources which have high resolution and high luminance, are driven at a high speed, include pixels with a size of less than 5 μm , and have a pitch of less than 3 μm , are applied, there is a need for new alternative solutions that can solve the above-described ultra-fine arrangement constraints.

[0011] Accordingly, although several impressive product demonstrations, which include 6 μm pixels using engineering monolithic epitaxy wafers manufactured through a low-temperature metal bonding process between a Si CMOS wafer and a micro-LED array wafer, have been recently released, mass production is considered impossible due to low quality and yield issues caused by

low-temperature metal bonding and the use of wafers with a small diameter of 6 inches or less. Above all, when ultra-fine pixels with a size of less than 3 μm for microdisplays are manufactured using conventional engineering monolithic epitaxy wafers through metal bonding, a patterning etching process faces even greater difficulties.

[0012] As another example, a novel engineering monolithic epitaxy wafer approach, which has made significant progress in solving a problem of a limitation on the brightness and resolution of LEDoS with Group III-V compound micro-LED light sources and simultaneously is capable of providing mass production and low-cost manufacturing solutions through the use of 12-inch diameter Si CMOS wafers, has been proposed. As shown in FIG. 3, specifically, in the corresponding technology, a process using an engineering monolithic epitaxy wafer is performed through the following four operations: {circle around (1)} an LED epitaxy cut to a final microdisplay panel **100** size (4 mm $\times$ 6 mm) is arranged and bonded onto a 12 inch Si blank wafer at a unit die level, and an LED growth wafer and a buffer layer are removed to perform planarization and leave only a 1.5 μm thick LED active layer on the large diameter Si blank wafer, {circle around (2)} the LED active layer left on the Si blank wafer is bonded to a Si CMOS wafer through multilayer metal bonding at a wafer level, {circle around (3)} the 12 inch Si blank wafer is removed, and then {circle around (4)} a micro-LED array that serves as a pixel is directly patterned on a Si CMOS wafer and manufactured.

[0013] However, in operation {circle around (1)}, when an LED epitaxy die is bonded onto the Si blank wafer, there is a limitation in that the die should be bonded by arranging a position on a Si CMOS integrated circuit (IC) wafer with the same size, in operation {circle around (2)}, when the LED active layer is bonded with multilayer metals including low-melting-point metals (Sn and In), there is a problem in that a discharge phenomenon in which low-melting-point metal components overflow relatively easily occurs to cause short circuit defects in which micro-LED sub-pixel arrays in a panel are electrically connected to each other or are connected to neighboring CMOS IC electrode pad arrays adjacent thereto, and in operation {circle around (4)}, there is a problem in that accurate ultra-fine patterning is difficult due to an opaque multilayer metal bonding layer, and defects are caused by the re-deposition of multilayer metal layer byproducts generated in a plasma dry process.

[0014] That is, the engineering monolithic epitaxy wafer approach presented in the above-described technologies is evaluated as a solution that is a step closer to implementing LEDoS based on ultra-small micro-LEDs with a pixel size of less than 5 μm . However, there are quality and yield issues due to the use of metals (low temperature, multilayer) in wafer bonding, it is very difficult to manufacture high-resolution microdisplays including ultra-fine pixels with a size of less than 3 μm , and there are also problems according to some arrangement processes. Thus, a new alternative is needed for this.

[0015] Furthermore, since a color filter is still applied to a vertically stacked tandem structure of conventional microdisplays to implement a full color, there are disadvantages in terms of color quality, process complexity, and productivity.

DISCLOSURE

Technical Problem

[0016] The present invention is directed to solving the above-described conventional problems and providing a vertically stacked light-emitting diode-on-silicon (LEDoS) microdisplay panel which eliminates the need for a process of arranging a light-emitting diode (LED) stack and a complementary metal oxide semiconductor (CMOS) electrode pad by using an engineering monolithic epitaxy wafer when a front wafer and a back wafer are bonded and simultaneously eliminates the need for a color filter due to each LED stack being able to emit only light of a specific color, and a method of manufacturing the same.

Technical Solution

[0017] According to the present invention, the above object is achieved by a vertically stacked

microdisplay panel that does not require a color filter including a back wafer having a plurality of complementary metal oxide semiconductor (CMOS) electrode pads arranged on an upper surface thereof, a plurality of light-emitting diode (LED) stacks in which a plurality of light-emitting portions and a plurality of bonding layers are vertically stacked on the back wafer and which are arranged on the plurality of CMOS electrode pads, and a common electrode formed on each of the plurality of LED stacks, wherein each of the plurality of LED stacks emits only light of a specific color by blocking the light generated from at least one light-emitting portion of the plurality of light-emitting portions or forming a bypass layer along an outer surface of the light-emitting portion to divert a current so that the current does not flow into the light-emitting portion.

[0018] In addition, the plurality of LED stacks may include a first LED stack configured to emit only light having a first color, a second LED stack configured to emit only light having a second color, and a third LED stack configured to emit only light having a third color, and each of the first LED stack, the second LED stack, and the third LED stack may include a first light-emitting portion bonded onto the CMOS electrode pad through a first bonding layer to emit light having the first color, a second light-emitting portion bonded onto the first light-emitting portion through a second bonding layer to emit light having the second color, and a third light-emitting portion bonded onto the second light-emitting portion through a third bonding layer to emit light having the third color.

[0019] In addition, the first LED stack may emit only the light having the first color by forming the bypass layer along outer surfaces of the third light-emitting portion and the second light-emitting portion to divert a current so that the current does not flow into the third light-emitting portion and the second light-emitting portion, the second LED stack may emit only the light having the second color by forming the bypass layer along the outer surface of the third light-emitting portion to divert a current so that the current does not flow into the third light-emitting portion and blocking the light generated from the first light-emitting portion, and the third LED stack may emit only the light having the third color by blocking the light generated from the second light-emitting portion and the first light-emitting portion.

[0020] In addition, the second LED stack may block the light generated from the first light-emitting portion through a metal layer formed on the first light-emitting portion, and the third LED stack may block the light generated from the second light-emitting portion and the first light-emitting portion through the metal layer formed on each of the second light-emitting portion and the first light-emitting portion.

[0021] In addition, the metal layer may include a lower layer which has an absorptive property to block light generated from below and an upper layer which has a reflective property to reflect light generated from above.

[0022] In addition, the bypass layer may be formed of a material that is optically transparent and electrically conductive.

[0023] In addition, the bonding layer is formed of a ceramic material that is optically transparent and electrically conductive.

[0024] In addition, the back wafer may be a silicon (Si) wafer.

[0025] In addition, an ohmic contact electrode may be formed on at least one of an upper surface and a lower surface of each of the light-emitting portions.

[0026] In addition, the ohmic contact electrode may be formed of a material that is optically transparent and electrically conductive.

[0027] According to the present invention, the above object is achieved by a method of manufacturing a vertically stacked microdisplay panel that does not require a color filter, the method including a preparing operation of preparing a plurality of front wafers which include a support wafer and a light-emitting portion and emit light having different colors and preparing a back wafer having a plurality of CMOS electrode pads arranged on an upper surface thereof, a stacking operation of repeating a process of bonding the front wafer onto the back wafer through

bonding layers and then removing the support wafer and vertically stacking the plurality of light-emitting portions and the bonding layers on the back wafer, an etching operation of etching and dividing the plurality of stacked light-emitting portions and bonding layers into preset units and arranging a plurality of LED stacks on the plurality of CMOS electrode pads, and a forming operation of forming a common electrode on the plurality of LED stacks, wherein each of the plurality of LED stacks emits only light of a specific color by blocking the light generated from at least one light-emitting portion of the plurality of light-emitting portions or forming a bypass layer along an outer surface of the light-emitting portion to divert a current so that the current does not flow into the light-emitting portion.

[0028] In addition, the plurality of front wafers may include a first front wafer including the support wafer and a first light-emitting portion, a second front wafer including the support wafer and a second light-emitting portion, and a third front wafer including the support wafer and a third light-emitting portion, and the plurality of LED stacks may include a first LED stack configured to emit only light having a first color, a second LED stack configured to emit only light having a second color, and a third LED stack configured to emit only light having a third color.

[0029] In addition, the stacking operation may include a first stacking operation of bonding the first front wafer onto the back wafer through a first bonding layer and then removing the support wafer to stack the first light-emitting portion on the back wafer, a second stacking operation of bonding the second front wafer onto the first light-emitting portion through a second bonding layer and then removing the support wafer to stack the second light-emitting portion on the first light-emitting portion, and a third stacking operation of bonding the third front wafer onto the second light-emitting portion through a third bonding layer and then removing the support wafer to stack the third light-emitting portion on the second light-emitting portion.

[0030] In addition, in the first stacking operation, after the support wafer is removed, a metal layer may be formed on a portion of the first light-emitting portion, in the second stacking operation, after the support wafer is removed, the metal layer may be formed on a portion of the second light-emitting portion, the second LED stack may block the light generated from the first light-emitting portion through the metal layer formed on the first light-emitting portion, and the third LED stack may block the light generated from the second light-emitting portion and the first light-emitting portion through the metal layer formed on each of the second light-emitting portion and the first light-emitting portion.

[0031] In addition, the metal layer may include a lower layer which has an absorptive property to block light generated from below and an upper layer which has a reflective property to reflect light generated from above.

[0032] In addition, the etching operation may include a first etching operation of etching and dividing the third light-emitting portion and the third bonding layer into first units, a second etching operation of etching and dividing the second light-emitting portion and the second bonding layer into second units, and a third etching operation of etching and dividing the first light-emitting portion and the first bonding layer into third units.

[0033] In addition, in the first etching operation, after the third light-emitting portion and the third bonding layer are etched and divided into the first units, the bypass layer may be formed along an outer surface of the third light-emitting portion at a portion in which the second LED stack is formed, in the second etching operation, after the second light-emitting portion and the first bonding layer are etched and divided into the second units, the bypass layer may be formed along outer surfaces of the third light-emitting portion and the second light-emitting portion at a portion in which the first LED stack is formed, the first LED stack may divert a current through the bypass layer formed along the outer surfaces of the third light-emitting portion and the second light-emitting portion so that the current does not flow into the third light-emitting portion and the second light-emitting portion, and the second LED stack may divert a current through the bypass layer formed along the outer surface of the third light-emitting portion such that the current does

not flow into the third light-emitting portion.

[0034] In addition, the bypass layer may be formed of a material that is optically transparent and electrically conductive.

[0035] In addition, the bonding layer is formed of a ceramic material that is optically transparent and electrically conductive.

[0036] In addition, the support wafer and the back wafer may be silicon (Si) wafers.

[0037] In addition, an ohmic contact electrode may be formed on at least one of an upper surface and a lower surface of each of the light-emitting portions.

[0038] In addition, the ohmic contact electrode may be formed of a material that is optically transparent and electrically conductive.

Advantageous Effects

[0039] According to the present invention, since a color filter is unnecessary despite the adoption of a vertically stacked tandem structure, the color quality of a microdisplay can be considerably improved, and process complexity and productivity can be considerably improved.

[0040] In addition, according to the present invention, unlike conventional monolithic integration methods or hybrid methods in which arrangement issues are present, since a stack on an engineering monolithic epitaxy wafer is etched and divided into preset units to allow a plurality of light-emitting diode (LED) stacks to be arranged on a plurality of complementary metal oxide semiconductor (CMOS) electrode pads, not only wafers with a small diameter of 6 inches or less, but also wafers with a large diameter of 8 inches or more can be used, which has the effect of considerably increasing the yield of products.

[0041] In addition, according to the present invention, since a ceramic material rather than metal is used for a bonding layer and an ohmic contact electrode, there are effects of considerably reducing the possibility of electrical short circuit defects and considerably increasing the reliability of a device. In addition, a plasma dry process of arranging an LED stack has effects in which etching is easy, and simultaneously the problem of re-deposition of etch by-products does not occur.

Moreover, the above-described ease of etching provides an advantage in that it is much more advantageous for manufacturing high-resolution microdisplays including ultra-fine pixels with a size of less than 3 μm .

[0042] In addition, according to the present invention, since a light-emitting portion, a bonding layer, and an ohmic contact electrode are all transparent to transmit visible light, there is an effect of no arrangement error issue in an exposure process.

[0043] Meanwhile, the effects of the present invention are not limited to the above-described effects, and various effects may be included within the range apparent to those skilled in the art from contents to be described below.

Description

DESCRIPTION OF DRAWINGS

[0044] FIG. 1 illustrates a structure of a conventional microdisplay panel.

[0045] FIG. 2 illustrates a conventional light-emitting diode-on-silicon (LEDoS) development approach.

[0046] FIG. 3 illustrates a conventional approach using an engineering monolithic epitaxy wafer.

[0047] FIG. 4 is an overall view of a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention.

[0048] FIG. 5 illustrates that only light of a specific color is emitted from each of a plurality of light-emitting diode (LED) stacks of the vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention.

[0049] FIG. 6 is a flowchart of a method of manufacturing a vertically stacked microdisplay panel

that does not require a color filter according to one embodiment of the present invention.

[0050] FIGS. **7** and **8** illustrate a process of manufacturing a plurality of front wafers in an n-side up form in the method of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention.

[0051] FIGS. **9** and **10** illustrate a process of manufacturing a plurality of front wafers in a p-side up form in the method of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention.

[0052] FIGS. **11** to **15** illustrate a process of manufacturing a vertically stacked microdisplay panel according to the method of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention.

[0053] [Modes of the Invention]

[0054] Hereinafter, some embodiments of the present invention will be described in detail with the accompanying exemplary drawings. When assigning reference numerals to components of each drawing, although the same components are illustrated in different drawings, the same components are given the same reference numerals as much as possible.

[0055] Further, in describing the present invention, a detailed description of related known configurations and functions will be omitted when it is determined that it may obscure the understanding of the embodiments of the present invention.

[0056] In addition, in describing components of the embodiment of the present invention, terms such as first, second, A, B, (a), and (b) may be used. These terms are used to distinguish one component from another component. However, the nature, the order, the sequence, or the number of components is not limited by these terms.

[0057] Hereinafter, a method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention will be described in detail with reference to the accompanying drawings.

[0058] FIG. **6** is a flowchart of the method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention. FIGS. **7** and **8** illustrate a process of manufacturing a plurality of front wafers **110** in an n-side up form in the method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention. FIGS. **9** and **10** illustrate a process of manufacturing the plurality of front wafers **110** in a p-side up form in the method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention. FIGS. **11** to **15** illustrate a process of manufacturing a vertically stacked microdisplay panel according to the method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention.

[0059] As shown in FIGS. **6** to **15**, the method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter according to one embodiment of the present invention includes a preparing operation **S110**, a stacking operation **S120**, an etching operation **S130**, and a forming operation **S140**.

[0060] The preparing operation **S110** is an operation of preparing a plurality of front wafers **110** and preparing a back wafer **140**.

[0061] The plurality of front wafers **110** may emit light having different colors, and the plurality of front wafers **110** may include a first front wafer **111** that emits light having a first color, a second front wafer **112** that emits light having a second color different from the first color, and a third front wafer **113** that emits light having a third color different from the first and second colors.

Meanwhile, the first color, the second color, and the third color may be, for example, a red color, a green color, and a blue color, respectively, but are not limited thereto, and may include various other colors.

[0062] Here, the plurality of front wafers **110** include, more specifically, the first front wafer **111**

including a support wafer S and a first light-emitting portion **121** disposed on the support wafer S, the second front wafer **112** including the support wafer S and a second light-emitting portion **122** disposed on the support wafer S, and the third front wafer **113** including the support wafer S and a third light-emitting portion **123** disposed on the support wafer S.

[0063] The support wafer S supports a light-emitting portion **120** (including the first light-emitting portion **121**, the second light-emitting portion **122**, and the third light-emitting portion **123**) disposed thereon. The support wafer S is provided as a Si wafer having a (111), (110), or (100) crystal plane to prevent quality issues due to a difference in thermal expansion coefficient from occurring when a front wafer **110** is bonded to the back wafer **140** to be described below.

[0064] The light-emitting portion **120** may generate light and emit blue light, green light, or red light. In the present invention, when the light-emitting portion **120** emits blue light or green light, binary, ternary, and quaternary compounds such as InN, InGaN, GaN, AlGaN, AlN, and AlGaInN, which are Group III (Al, Ga, and In) nitride semiconductors among Group III-V compound semiconductors, may be disposed at an appropriate position and order on an initial growth wafer G and epitaxially grown.

[0065] In particular, in order to emit blue light or green light, a high-quality Group III nitride semiconductor such as InGaN having a high In composition should be preferentially formed on a Group III nitride semiconductor consisting of GaN, AlGaN, AlN, or AlGaInN, but the present invention is not limited thereto.

[0066] In addition, in the present invention, when the light-emitting portion **120** emits red light, binary, ternary, and quaternary compounds such as InP, InGaP, GaP, AlInP, AlGaP, AlP, and AlGaInP, which are Group III (Al, Ga, and In) phosphide semiconductors among Group III-V compound semiconductors, may be disposed at an appropriate position and order on the initial growth wafer G and epitaxially grown. In addition, in recent years, in order to further improve the development of equipment and process technologies and the value of display panel products, when red light is emitted, rather than a Group III phosphide semiconductor, a high-quality Group III nitride semiconductor such as InGaN with a high In composition of 30% or more may be preferentially formed on a Group III nitride semiconductor consisting of GaN, AlGaN, AlN, and AlGaInN.

[0067] In particular, in order to emit red light, a high-quality Group III phosphide semiconductor having a high In composition such as InGaP should be preferentially formed on a Group III phosphide semiconductor consisting of GaP, AlInP, AlGaP, AlP, AlGaInP, but the present invention is not limited thereto. Hereinafter, for convenience of description, a Group III nitride semiconductor will be mainly described.

[0068] Each light-emitting portion **120** may include, more specifically, a first semiconductor region **1201** (for example, a p-type semiconductor region), an active region **1203** (for example, a multi-quantum well (MQW)), and a second semiconductor region **1202** (for example, an n-type semiconductor region). The light-emitting portion **120** may have a structure in which the second semiconductor region **1202**, the active region **1203**, and the first semiconductor region **1201** are sequentially and epitaxially grown on the growth substrate G and may typically have an overall thickness of about 5.0 μm to about 8.0 μm by ultimately including a plurality of layers of Group III nitrides, but the present invention is not limited thereto.

[0069] Each of the first semiconductor region **1201**, the active region **1203**, and the second semiconductor region **1202** may be provided as a single layer or multiple layers, and although not shown, before the light-emitting portion **120** is epitaxially grown on the growth wafer G, necessary layers such as a buffer layer may be added to improve the quality of the epitaxially grown light-emitting portion **120**. For example, the buffer layer may typically have a thickness of about 4.0 μm by including a compliant layer (CL) consisting of a nucleation layer (NL) and an un-doped semiconductor region to relieve stress and improve thin film quality. In addition, when the growth wafer G is removed using a laser lift-off (LLO) technique, a sacrificial layer may be separately and

additionally provided between the NL and the un-doped semiconductor region, and a seed layer (SL) may also serve as the sacrificial layer.

[0070] The second semiconductor region **1202** has second conductivity (n-type) and is formed on the growth wafer G. This second semiconductor region **1202** may have a thickness of 2.0 μm to 3.5 μm .

[0071] The active region **1203** generates light using the recombination of electrons and holes and is formed on the second semiconductor region **1202**. The active region **1203** may be provided as a plurality of layers to have a thickness of several tens nm.

[0072] The first semiconductor region **1201** has first conductivity (p-type) and is formed on the active region **1203**. The first semiconductor region **1201** may be provided as a plurality of layers to have a thickness of several tens of nm to several μm , and an upper surface thereof may have gallium polarity (Ga-polarity).

[0073] That is, the active region **1203** is interposed between the first semiconductor region **1201** and the second semiconductor region **1202** so that holes of the first semiconductor region **1201**, which is a p-type semiconductor region, recombine with electrons of the second semiconductor region **1202**, which is an n-type semiconductor region, in the active region **1203** to generate light.

[0074] In addition, before the front wafer **110** and the back wafer **140** are bonded through a bonding layer **130**, an ohmic contact electrode **124**, which is optically transparent and electrically conductive and is in ohmic contact with and electrically connected to the light-emitting portion **120**, may be formed on at least one of an upper surface and a lower surface of the light-emitting portion **120**, which will be described below.

[0075] Meanwhile, the front wafer **110** of the present invention may be manufactured in an n-side up form in which the second semiconductor region **1202** having the second conductivity (n type) is exposed to the outside or in a p-side up form in which the first semiconductor region **1201** having the first conductivity (p type) is exposed to the outside.

[0076] As shown in FIGS. 7 and 8, a case in which the front wafer **110** of the present invention is manufactured in the n-side up form in which the second semiconductor region **1202** having the second conductivity (n type) is exposed to the outside is a case in which the growth wafer G is removed by performing bonding once, and a process is as follows.

[0077] First, when the light-emitting portion **120** emits blue light or green light, the second semiconductor region **1202**, the active region **1203**, and the first semiconductor region **1201** are sequentially stacked on a sapphire (α -phase Al_2O_3) growth wafer G, which is a wafer that is optically transparent to (theoretically) transmit 100% of a laser beam (single wavelength light) without absorbing the laser beam and has high temperature resistance, to epitaxially grow the light-emitting portion **120**, an ohmic contact electrode **124**, which is transparent and conductive, is formed on an upper surface of the first semiconductor region **1201**, and then a silicon (Si) support wafer S having a (111), (110), or (100) crystal plane is bonded to the ohmic contact electrode **124** through a bonding layer B. Thereafter, the growth wafer G is separated from the light-emitting portion **120** using an LLO technique, the second semiconductor region **1202** is etched to reduce a thickness of the second semiconductor region **1202**, an ohmic contact electrode **124**, which is transparent and conductive, is formed on a lower surface of the second semiconductor region **1202** with the reduced thickness, and then a bonding layer **130** is deposited and formed on the lower ohmic contact electrode **124**, thereby preparing the front wafer **110** with an n-side up form.

[0078] On the other hand, the light-emitting portion **120** that emits blue or green light may be formed on silicon (Si) growth wafer G having a (111) crystal plane instead of the sapphire (α -phase Al_2O_3) growth wafer G, and in this case, the silicon (Si) growth wafer G may be separated and removed through mechanical polishing or a chemical etching technique (chemical lift-off (CLO)).

[0079] In addition, when the light-emitting portion **120** emits red light, the second semiconductor region **1202**, the active region **1203**, and the first semiconductor region **1201** are sequentially stacked on a GaAs growth wafer G to epitaxially grow the light-emitting portion **120**, an ohmic

contact electrode **124**, which is transparent and conductive, is formed on the upper surface of the first semiconductor region **1201**, and then the silicon (Si) support wafer S having a (111), (110), or (100) crystal plane is bonded to the ohmic contact electrode **124** through a bonding layer B. Thereafter, the growth wafer G is separated from the light-emitting portion **120** using a CLO technique, the second semiconductor region **1202** is etched to reduce a thickness of the second semiconductor region **1202**, an ohmic contact electrode **124**, which is transparent and conductive, is formed on the lower surface of the second semiconductor region **1202** with the reduced thickness, and then a bonding layer **130** is deposited and formed on the lower ohmic contact electrode **124**, thereby preparing the front wafer **110** with an n-side up form.

[0080] Accordingly, when the front wafer **110** has the n-side up form, the front wafer **110** has a structure in which the silicon (Si) support wafer S having a (111), (110), or (100) crystal plane, the bonding layer B, the ohmic contact electrode **124**, the first semiconductor region **1201**, the active region **1203**, the second semiconductor region **1202**, the ohmic contact electrode **124**, and the bonding layer **130** are sequentially stacked. The silicon (Si) support wafer S has no difference in thermal expansion coefficient when the front wafer **110** is bonded to the silicon (Si) back wafer **140** later, thereby contributing to stabilizing the quality of a vertically stacked microdisplay panel.

[0081] In addition, as shown in FIGS. **9** and **10**, a case in which the front wafer **110** of the present invention is manufactured in the p-side up form in which the first semiconductor region **1201** having the first conductivity (p type) is exposed to the outside is a case in which the growth wafer G and a temporary wafer T are removed by performing bonding twice, and a process is as follows.

[0082] First, when the light-emitting portion **120** emits blue light or green light, the second semiconductor region **1202**, the active region **1203**, and the first semiconductor region **1201** are sequentially stacked on a sapphire (α -phase Al_2O_3) growth wafer G, which is a wafer that is optically transparent to (theoretically) transmit 100% of a laser beam (single wavelength light) without absorbing the laser beam and has high temperature resistance, to epitaxially grow the light-emitting portion **120**, an ohmic contact electrode **124**, which is transparent and conductive, is formed on the upper surface of the first semiconductor region **1201**, and then the sapphire temporary wafer T, which is a wafer that is optically transparent and has high temperature resistance, is bonded to the ohmic contact electrode through an adhesive layer A. Thereafter, the growth wafer G is separated from the light-emitting portion **120** using an LLO technique, the second semiconductor region **1202** is etched to reduce a thickness of the second semiconductor region **1202**, an ohmic contact electrode **124**, which is transparent and conductive, is formed on the lower surface of the second semiconductor region **1202** with the reduced thickness, and then the silicon (Si) support wafer S having a (111), (110), or (100) crystal plane is bonded to the ohmic contact electrode **124** through a bonding layer B. Thereafter, the temporary wafer T is separated from the adhesive layer A using an LLO technique, the adhesive layer A is etched and removed, and a bonding layer **130** is deposited and formed on the upper ohmic contact electrode **124**, thereby preparing the front wafer **110** with a p-side up form. In addition, when Si having a (111), (110) or (100) crystal plane is used as the temporary wafer T instead of sapphire, the temporary wafer T is separated and removed through a CLO process instead of an LLO process.

[0083] On the other hand, the light-emitting portion **120** that emits blue or green light may be formed on silicon (Si) growth wafer G having a (111) crystal plane instead of the sapphire (α -phase Al_2O_3) growth wafer G, and in this case, the Si growth wafer G and the support wafer S are separated and removed through mechanical polishing or a CLO technique.

[0084] In addition, when the light-emitting portion **120** emits red light, the second semiconductor region **1202**, the active region **1203**, and the first semiconductor region **1201** are sequentially stacked on a GaAs growth wafer G to epitaxially grow the light-emitting portion **120**, an ohmic contact electrode **124**, which is transparent and conductive, is formed on the upper surface of the first semiconductor region **1201**, and then the sapphire support wafer S, which is a wafer that is an optically transparent and has high temperature resistance, is bonded to the ohmic contact electrode

124 through a bonding layer B. Thereafter, the growth wafer G is separated from the light-emitting portion 120 using a CLO technique, the second semiconductor region 1202 is etched to reduce a thickness of the second semiconductor region 1202, an ohmic contact electrode 124, which is transparent and conductive, is formed on the lower surface of the second semiconductor region 1202 with the reduced thickness, and then the silicon (Si) support wafer S having a (111), (110), or (100) crystal plane is bonded to the ohmic contact electrode 124 through a bonding layer B. Thereafter, the temporary wafer T is separated from the adhesive layer A using an LLO technique, the adhesive layer A is etched and removed, and a bonding layer 130 is deposited and formed on the upper ohmic contact electrode 124, thereby preparing the front wafer 110 with a p-side up form. In addition, when Si having a (111), (110) or (100) crystal plane is used as the temporary wafer T instead of sapphire, the temporary wafer T is separated and removed through a CLO process instead of an LLO process.

[0085] Accordingly, when the front wafer 110 has the p-side up form, the front wafer 110 has a structure in which the silicon (Si) support wafer S having a (111), (110), or (100) crystal plane, the bonding layer B, the ohmic contact electrode 124, the second semiconductor region 1202, the active region 1203, the first semiconductor region 1201, the ohmic contact electrode 124, and the bonding layer 130 are sequentially stacked. The silicon (Si) support wafer S has no difference in thermal expansion coefficient when the front wafer 110 is bonded to the silicon (Si) back wafer 140 later, thereby contributing to stabilizing the quality of a vertically stacked microdisplay panel.

[0086] Furthermore, in a process of manufacturing the front wafer 110 with the p-side up or n-side up form described above, before the ohmic contact electrode 124 is formed on a surface of the first semiconductor region 1201 or a surface of the second semiconductor region 1202, when the surface of the first semiconductor region 1201 is exposed (p-side up form) or the surface of the second semiconductor region 1202 is exposed (n-side up form), each surface may be polished and smoothly planarized through mechanical polishing (MP) or chemical-mechanical polishing (CMP) to have a smooth surface.

[0087] Meanwhile, the ohmic contact electrode 124 of the front wafer 110 is formed of a material having transparency and conductivity. When the ohmic contact electrode 124 is formed in contact with the first semiconductor region 1201 which is a p-type semiconductor, a material of the ohmic contact electrode 124 may include NiO, PtO, PdO, AgO₂, Au, Rh₂O₃, RuO₂, In₂O₃, SnO₂, zinc oxide (ZnO), indium zinc oxide (IZO), indium tin oxide (ITO), and indium germanium zinc oxide (IGZO). When the ohmic contact electrode 124 is formed in contact with the second semiconductor region 1202 which is an n-type semiconductor, the material of the ohmic contact electrode 124 may include TiN, CrN, VN, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO. Furthermore, since the surface of the second semiconductor region 1202 having nitrogen polarity (N-polarity) has a much higher surface roughness than the surface of the first semiconductor region 1201 having gallium polarity (Ga-polarity), it is preferable to introduce a CMP process of polishing and planarizing the surface of the second semiconductor region 1202 before forming the ohmic contact electrode 124 which is transparent and conductive.

[0088] In addition, a surface of the ohmic contact electrode 124 formed on the front wafer 110 may also be polished and smoothly planarized through MP or CMP.

[0089] The back wafer 140 is a CMOS wafer in which, as an active driving IC driven through an active matrix (AM) method, a plurality of CMOS electrode pads 141 are arrayed on an upper surface thereof. A passivation layer may be formed between the plurality of CMOS electrode pads 141.

[0090] Here, the back wafer 140 is provided as a Si wafer having a (100) crystal plane and is preferably provided as an 8-inch or 12-inch Si wafer according to a standard CMOS IC process.

[0091] The stacking operation S120 is an operation of vertically stacking a plurality of light-emitting portions 212 and a plurality of bonding layers 230 on the back wafer 140 by repeating a process of bonding an inverted front wafer 110 onto the back wafer 140 through the bonding layer

130 such that the light-emitting portion **120** of the front wafer **110** faces the CMOS electrode pad **141** of the back wafer **140**, that is, the light-emitting portion **120** of the front wafer **110** and the CMOS electrode pad **141** of the back wafer **140** face each other, and then removing the support wafer S.

[0092] Here, since the support wafer S of the front wafer **110** is a Si wafer having a (111), (110), or (100) crystal plane, and the back wafer **140** is also a Si wafer having a (100) crystal plane, there is no difference in thermal expansion coefficient during bonding, thereby contributing to stabilizing the quality of a vertically stacked microdisplay panel.

[0093] In this case, the stacking operation **S120** uses properties in which smooth surfaces adhere to each other due to van der Waals forces without using a high voltage or an external electric field. Accordingly, it is preferable that, before the front wafer **110** and the back wafer **140** are bonded through the bonding layer **130**, a CMP process is introduced so that the roughness of each bonding surface is very low ($R_q < 0.5 \text{ nm}$ @ $2 \mu\text{m} \times 2 \mu\text{m}$) and there are no particles such as impurities between surfaces. To this end, in the stacking operation **S120**, before the front wafer **110** is bonded to the back wafer **140**, surfaces of the bonding layer **130** of the front wafer **110** and the bonding layer **230** of the back wafer **140** may each be polished and smoothly planarized through MP or CMP.

[0094] Here, the bonding layer **130** (including a first bonding layer **131**, a second bonding layer **132**, and a third bonding layer **133** described below) is formed of a ceramic material that is optically transparent and electrically conductive, that is, transparent and conductive. Here, the term “optically transparent” means being transparent (transmittance of 80% or more) or translucent (transmittance of 50% or more) in a wavelength band of light (including visible light) used in an optical exposure (photolithography) process, and the term “electrically conductive” means having an electrical resistance of less than $10^{-3} \text{ } (\Omega/\text{cm})$. The ceramic material with such transparency and conductivity includes a transparent conductive oxide (TCO), a transparent conductive nitride (TCN), and a transparent conductive oxide nitride (TCON).

[0095] In this case, when the ceramic material is a TCO, the ceramic material may include In_2O_3 , SnO_2 , ZnO , IZO, ITO, and IGZO, when the ceramic material is a TCN, the ceramic material may include TiN , CrN , and VN , and when the ceramic material is a TCON, the ceramic material may include InON , SnON , ZnON , IZON , ITON , and IGZON .

[0096] As shown in FIGS. **11** to **13**, the stacking operation **S120** includes, in more detail, a first stacking operation, a second stacking operation, and a third stacking operation.

[0097] The first stacking operation is an operation of bonding the first front wafer **111** onto the back wafer **140** through the first bonding layer **131** such that the first light-emitting portion **121** of the first front wafer **111** with an n-side up (or p-side up) form faces the CMOS electrode pad **141** of the back wafer **140**, removing the support wafer S using MP, a CLO technique, and the like, and then etching and removing the bonding layer B to stack the first light-emitting portion **121** on the back wafer **140**.

[0098] In this case, in the first stacking operation, after the support wafer S is removed, a first metal layer **171** may be formed on a portion of the first light-emitting portion **121**, that is, at portions in which a second LED stack **220** and a third LED stack **230** are to be formed.

[0099] The second stacking operation is an operation of bonding the second front wafer **112** onto the back wafer **140**, to which the first light-emitting portion **121** having ohmic contact electrodes **124** formed on upper and lower surfaces thereof is bonded, through the second bonding layer **132** such that the second light-emitting portion **122** of the second front wafer **112** with an n-side up (or p-side up) form faces the CMOS electrode pad **141** of the back wafer **140**, removing the support wafer S using MP and a CLO technique, and then etching and removing the bonding layer B to stack the second light-emitting portion **122** on the first light-emitting portion **121**.

[0100] In this case, in the second stacking operation, after the support wafer S is removed, a second metal layer **172** may be formed on a portion of the second light-emitting portion **122**, that is, at a

portion in which the third LED stack **230** is to be formed.

[0101] Meanwhile, each of the first metal layer **171** and the second metal layer **172** described above may be composed of a single layer or multiple layers. When each of the first metal layer **171** and the second metal layer **172** composed of multiple layers, a lower layer may have an absorptive property to block light generated from below, and an upper layer may have a reflective property to reflect light generated from above. For example, Ag/Ni may correspond to the multiple layers. In addition, each of the first metal layer **171** and the second metal layer **172** may include an adhesive layer formed of Ti, Cr, Ni, or the like to improve adhesiveness. In addition, considering reflection/absorption, a thickness of each of the first metal layer **171** and the second metal layer **172** is preferably the minimum thickness to block 100% of light therebelow. This is because when the thickness is thick, there is a difficulty in a transparent conductive bonding and planarizing process.

[0102] In the third stacking operation, the third front wafer **113** is bonded onto the back wafer **140**, to which the second light-emitting portion **122** having ohmic contact electrodes **124** formed on upper and lower surfaces thereof is bonded, through the third bonding layer **133** such that the third light-emitting portion **123** of the third front wafer **113** with an n-side up (or p-side up) form faces the CMOS electrode pad **141** of the back wafer **140**, the support wafer S is removed using MP and a CLO technique, and then the bonding layer B is etched and removed, thereby obtaining a structure in which the back wafer, the first bonding layer **131**, the first light-emitting portion **121** having ohmic contact electrodes **124** formed on upper and lower surfaces thereof, the second bonding layer **132**, the second light-emitting portion **122** having ohmic contact electrodes **124** formed on upper and lower surfaces thereof, the third bonding layer **133**, and the third light-emitting portion **123** having ohmic contact electrodes **124** formed on upper and lower surfaces thereof are vertically stacked, and the first metal layer **171** and the second metal layer **172** are formed on portions of the first light-emitting portion **121** and the second light-emitting portion **122**, respectively.

[0103] That is, in the present invention, considering a wavelength of light, it is preferable that first color light of the first light-emitting portion **121** of a lower layer is red light with a long wavelength, second color light of the second light-emitting portion **122** of an intermediate layer is green light, and third color light of the third light-emitting portion **123** of an upper layer is blue light with a short wavelength, but the present invention is not limited thereto.

[0104] Afterward, in the stacking operation **S120**, after the front wafer **110** is bonded to the back wafer **140**, it is necessary perform heat treatment on the bonding layer **130** at a temperature of less than 400° C. such that a CMOS circuit of the back wafer **140** is not damaged.

[0105] The etching operation **S130** is an operation of etching and dividing the plurality of stacked light-emitting portions **120** and bonding layers **130** into preset units to place and arrange the plurality of LED stacks **200** on the plurality of CMOS electrode pads **141** and an operation that eliminates the need for a conventional process of arranging the LED stacks of the front wafer **110** and the CMOS electrode pads **141** of the back wafer **140**.

[0106] That is, in the etching operation **S130**, the light-emitting portion **120**, the bonding layer **130**, and the ohmic contact electrode **124** are vertically etched until a surface of the back wafer **140** or an area adjacent thereto is exposed to arrange the plurality of LED stacks **200** on the arrayed, that is, arranged, CMOS electrode pads **141**. Here, the preset unit may refer to a pixel or subpixel unit and may refer to a diameter (width) of the plurality of LED stacks **200**.

[0107] In this case, the light-emitting portion **120**, the bonding layer **130**, and the ohmic contact electrode **124** of the present invention are all transparent to transmit visible light, and thus there is an advantage in that there is no arrangement error issue in an exposure process. In addition, since a ceramic material is used rather than a metal, both the bonding layer **130** and the ohmic contact electrode **124** of the present invention are easy to etch in a plasma dry process, and there is an advantage in that a problem of re-deposition of etch by-products does not occur.

[0108] Meanwhile, the plurality of LED stacks **200** include a first LED stack **210** for emitting only light having a first color, the second LED stack **220** for emitting only light having a second color, and the third LED stack **230** for emitting only light having a third color.

[0109] As shown in FIGS. **14** and **15**, the etching operation **S130** includes, in more detail, a first etching operation, a second etching operation, and a third etching operation.

[0110] The first etching operation is an operation of etching and dividing the third light-emitting portion **123** and the third bonding layer **133** into first units.

[0111] In this case, in the first etching operation, the third light-emitting portion **123** and the third bonding layer **133** may be etched and divided into the first units, and then a second bypass layer **182** may be formed along an outer surface of the third light-emitting portion **123** in the second LED stack part (including an outer surface of the third bonding layer **133**). In this case, an upper side of the second bypass layer **182** may be in contact with and electrically connected to a common electrode **160**, and both ends thereof may be electrically connected to the ohmic contact electrode **124** of the second light-emitting portion **122** or the third bonding layer **133**.

[0112] The second etching operation is an operation of, after etching and dividing the third light-emitting portion **123** and the third bonding layer **133**, etching and dividing the second light-emitting portion **122** and the second bonding layer **132** into second units.

[0113] In this case, in the second etching operation, the second light-emitting portion **122** and the second bonding layer **132** may be etched and divided into the second units, and then a first bypass layer **181** may be formed along outer surfaces of the third light-emitting portion **123** and the second light-emitting portion **122** in the first LED stack **210** part (including outer surfaces of the third bonding layer **133** and the second bonding layer **132**). In this case, an upper side of the first bypass layer **181** may be in contact with and electrically connected to the common electrode **160**, and both ends thereof may be electrically connected to the ohmic contact electrode **124** of the first light-emitting portion **121** or the second bonding layer **132**.

[0114] Meanwhile, each of the first bypass layer **181** and the second bypass layer **182** described above may be formed of an optically transparent and electrically conductive material and may be preferably formed of a material having low resistance and high transmittance characteristics. Such materials may include In₂O₃, SnO₂, ZnO, IZO, ITO, IGZO, and the like, but the present invention is not limited thereto.

[0115] The third etching operation is an operation of, after etching and dividing the second light-emitting portion **122** and the second bonding layer **132**, etching and dividing the first light-emitting portion **121** and the first bonding layer **131** into third units. Meanwhile, the first unit may be smaller than the second unit, and the second unit may be smaller than the third unit (the third light-emitting portion **123** may have a smaller diameter than the second light-emitting portion **122**, and the second light-emitting portion **122** may have a smaller diameter than the first light-emitting portion **121**). That is, a light-emitting area of the second LED stack **220** may be smaller than a light-emitting area of the first LED stack **210**, and a light-emitting area of the third LED stack **230** may be smaller than the light-emitting area of the second LED stack **220**, but the present invention is not limited thereto.

[0116] Accordingly, among the plurality of LED stacks **200**, the first LED stack **210** may emit only light having the first color by diverting the current flow into the third light-emitting portion **123** and the second light-emitting portion **122** through the first bypass layer **181**, and here, the first bypass layer **181** may block the current flow into the third light-emitting portion **123** and the second light-emitting portion **122** by diverting the current flowing into the third light-emitting portion **123** and the second light-emitting portion **122** to the first light-emitting portion **121**. That is, the first bypass layer **181** serves as a short path for the third light-emitting portion **123** and the second light-emitting portion **122**.

[0117] In addition, the second LED stack **220** may emit only light having the second color by blocking the light generated from the first light-emitting portion **121** through the first metal layer

171 formed on the first light-emitting portion **121** and diverting the current flow into the third light-emitting portion **123** through the second bypass layer **182**. Here, the second bypass layer **182** may block the current flow into the third light-emitting portion **123** by diverting the current flowing into the third light-emitting portion **123** to the second light-emitting portion **122**. That is, the second bypass layer **182** serves as a short path for the third light-emitting portion **123**.

[0118] In addition, the third LED stack **230** may emit only light having the third color by blocking the light generated from the first light-emitting portion **121** and the second light-emitting portion **122** through the first metal layer **171** formed on the first light-emitting portion **121** and the second metal layer **172** formed on the second light-emitting portion **122**.

[0119] That is, each of the plurality of LED stacks **200** emits only light of a specific color by blocking the light generated from at least one of the plurality of light-emitting portions **120** through the above-described metal layer or bypass layer or blocking current flow into at least one of the plurality of light-emitting portions **120**.

[0120] In addition, in the present invention, an operating voltage is generated differently for each of the plurality of LED stacks **200**. Specifically, in the first LED stack **210**, current flow into the third light-emitting portion **123** and the second light-emitting portion **122** is blocked so that a voltage (for example, 3 V) is applied to only one layer, i.e., the first light-emitting portion **121**, in the second LED stack **220**, current flow into the third light-emitting portion **123** is blocked, and the second light-emitting portion **122** and the first light-emitting portion **121** are connected in series so that a voltage (for example, 6 V) is applied to two layers, and in the third LED stack **230**, all layers of the light-emitting portions **120** are connected in series so that a voltage (for example, 9 V) is applied to three layers.

[0121] The forming operation **S140** is an operation of forming a mold portion **150** that fills a space between the plurality of arranged LED stacks **200**, and then forming the common electrode **160** on the plurality of LED stacks **200**.

[0122] More specifically, in the forming operation **S140**, after the mold portion **150** is formed to fill the space between the plurality of arranged LED stacks **200** and support the LED stacks **200** and the mold portion **150** is etched such that upper portions of the plurality of LED stacks **200** are exposed, the common electrode **160** is formed on the exposed upper portions of the plurality of LED stacks **200**, thereby completing a vertically stacked LEDoS structure. Here, similar to the ohmic contact electrode **124**, the common electrode **160** may be formed of a material that is transparent and conductive. When the common electrode **160** is an anode, a material of the common electrode **160** may include NiO, PtO, PdO, AgO₂, Au, Rh₂O₃, RuO₂, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO, and when the common electrode **160** is a cathode, the material of the common electrode **160** may include TiN, CrN, VN, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO.

[0123] In addition, a surface of the common electrode **160** may also be polished and smoothly planarized through MP or CMP.

[0124] Furthermore, although not shown, a protection layer may be additionally formed using a transparent organic material to protect the common electrode **160** from the atmospheric environment.

[0125] Hereinafter, a vertically stacked microdisplay panel **100** that does not require a color filter according to one embodiment of the present invention will be described in detail with reference to the accompanying drawings.

[0126] FIG. 4 is an overall view of the vertically stacked microdisplay panel **100** that does not require a color filter according to one embodiment of the present invention. FIG. 5 illustrates that only light of a specific color is emitted from each of a plurality of LED stacks **200** of the vertically stacked microdisplay panel **100** that does not require a color filter according to one embodiment of the present invention.

[0127] As shown in FIGS. 4 and 5, the vertically stacked microdisplay panel **100** that does not require a color filter according to one embodiment of the present invention includes a back wafer

140, the plurality of LED stacks **200**, a mold portion **150**, and a common electrode **160**.

[0128] The back wafer **140** is a CMOS wafer in which, as an active driving IC driven through an AM method, a plurality of CMOS electrode pads **141** are arrayed on an upper surface thereof. A passivation layer may be formed between the plurality of CMOS electrode pads **141**.

[0129] Here, the back wafer **140** is provided as a Si wafer having a (100) crystal plane and is preferably provided as an 8-inch or 12-inch Si wafer according to a standard CMOS IC process.

[0130] The plurality of LED stacks **200** are formed by vertically stacking a plurality of light-emitting portions **120** and a plurality of bonding layers **130** on the back wafer **140** and are arranged on the plurality of CMOS electrode pads **141**.

[0131] The plurality of LED stacks **200** include a first LED stack **210** for emitting only light having a first color, a second LED stack **220** for emitting only light having a second color, and a third LED stack **230** for emitting only light having a third color. Meanwhile, the first color, the second color, and the third color may be, for example, a red color, a green color, and a blue color, respectively, but are not limited thereto, and may include various other colors.

[0132] In addition, the first LED stack **210**, the second LED stack **220**, and the third LED stack **230** may each have a tandem structure in which the plurality of light-emitting portions **120** and the plurality of bonding layers **130** are vertically stacked, and more specifically, may include a first light-emitting portion **121** bonded onto the CMOS electrode pad **141** through a first bonding layer **131** to emit light having the first color, a second light-emitting portion **122** bonded onto the first light-emitting portion **121** through a second bonding layer **132** to emit light having the second color, and a third light-emitting portion **123** bonded onto the second light-emitting portion **122** through a third bonding layer **133** to emit light having the third color.

[0133] That is, in the present invention, considering a wavelength of light, it is preferable that first color light of the first light-emitting portion **121** of a lower layer is red light with a long wavelength, second color light of the second light-emitting portion **122** of an intermediate layer is green light, and third color light of the third light-emitting portion **123** of an upper layer is blue light with a short wavelength, but the present invention is not limited thereto.

[0134] In the present invention, each of the first light-emitting portion **121**, the second light-emitting portion **122**, and the third light-emitting portion **123** may be stacked in an n-side up form or a p-side up form, and an ohmic contact electrode **124** that is in ohmic contact with and electrically connected to the light-emitting portion **120** may be formed on at least one of an upper surface and a lower surface of each of the first light-emitting portion **121**, the second light-emitting portion **122**, and the third light-emitting portion **123**.

[0135] The ohmic contact electrode **124** is formed of a material which is transparent and conductive. When the ohmic contact electrode **124** is formed in contact with a first semiconductor region **1201** which is a p-type semiconductor, a material of the ohmic contact electrode **124** may include NiO, PtO, PdO, AgO₂, Au, Rh₂O₃, RuO₂, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO. When the ohmic contact electrode **124** is formed in contact with the second semiconductor region **1202** which is an n-type semiconductor, a material of the ohmic contact electrode **124** may include TiN, CrN, VN, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO. Furthermore, since a surface of a second semiconductor region **1202** having nitrogen polarity (N-polarity) has a much higher surface roughness than a surface of the first semiconductor region **1201** having gallium polarity (Ga-polarity), it is preferable to introduce a CMP process of polishing and planarizing the surface of the second semiconductor region **1202** before forming the ohmic contact electrode **124** which is transparent and conductive.

[0136] In addition, a surface of the ohmic contact electrode **124** formed on the front wafer **110** may also be polished and smoothly planarized through MP or CMP.

[0137] Meanwhile, the following contents regarding the light-emitting portion **120** are the same as those of the method **S100** of manufacturing a vertically stacked microdisplay panel that does not require a color filter, and thus redundant descriptions thereof will be omitted.

[0138] In addition, the bonding layer **130** (including the first bonding layer **131**, the second bonding layer **132**, and the third bonding layer **133**) is formed of a ceramic material that is optically transparent and electrically conductive, that is, transparent and conductive. Here, the term “optically transparent” means being transparent (transmittance of 80% or more) or translucent (transmittance of 50% or more) in a wavelength band of light (including visible light) used in an optical exposure (photolithography) process, and the term “electrically conductive” means having an electrical resistance of less than 10^{-3} (Ω/cm). The ceramic material with such transparency and conductivity includes a TCO, a TCN, and a TCON.

[0139] In this case, when the ceramic material is a TCO, the ceramic material may include In_2O_3 , SnO_2 , ZnO , IZO, ITO, and IGZO, when the ceramic material is a TCN, the ceramic material may include TiN, CrN, and VN, and when the ceramic material is a TCON, the ceramic material may include InON, SnON, ZnON, IZON, ITON, and IGZON.

[0140] In the present invention, each of the plurality of LED stacks **200** may emit only light of a specific color without a color filter by blocking the light generated from at least one of the plurality of light-emitting portions **120** or forming a bypass layer along an outer surface of the light-emitting portion to divert a current so that the current does not flow into the light-emitting portion.

[0141] More specifically, among the plurality of LED stacks **200**, the first LED stack **210** may emit only light having the first color by diverting the current flow into the third light-emitting portion **123** and the second light-emitting portion **122** through a first bypass layer **181**, and here, the first bypass layer **181** may be formed along outer surfaces of the etched third light-emitting portion **123** and second light-emitting portion **122** (including outer surfaces of the third bonding layer **133** and the second bonding layer **132**) to block the current flow into the third light-emitting portion **123** and the second light-emitting portion **122** by diverting the current flowing into the third light-emitting portion **123** and the second light-emitting portion **122** to the first light-emitting portion **121**. In this case, an upper side of the first bypass layer **181** may be in contact with and electrically connected to the common electrode **160**, and both ends thereof may be electrically connected to the ohmic contact electrode **124** of the first light-emitting portion **122** or the second bonding layer **132**. That is, the first bypass layer **181** serves as a short path for the third light-emitting portion **123** and the second light-emitting portion **122**.

[0142] In addition, the second LED stack **220** may emit only light having the second color by blocking the light generated from the first light-emitting portion **121** through a first metal layer **171** and diverting the current flow into the third light-emitting portion **123** through a second bypass layer **182**. Here, the first metal layer **171** may be formed on the first light-emitting portion **121** to block the light generated from the first light-emitting portion **121**, and the second bypass layer **182** may be formed along an outer surface of the etched third light-emitting portion **123** (including an outer surface of the third bonding layer **133**) to divert the current flowing into the third light-emitting portion **123** to the second light-emitting portion **122**, thereby blocking the current flow into the third light-emitting portion **123**. In this case, an upper side of the second bypass layer **182** may be in contact with and electrically connected to the common electrode **160**, and both ends thereof may be electrically connected to the ohmic contact electrode **124** of the second light-emitting portion **122** or the third bonding layer **133**. That is, the second bypass layer **182** serves as a short path for the third light-emitting portion **123**.

[0143] In addition, the third LED stack **230** may emit only light having the third color by blocking the light generated from the first light-emitting portion **121** and the second light-emitting portion **122** through the first metal layer **171** and a second metal layer **172**. Here, the first metal layer **171** may be formed on the first light-emitting portion **121** to block the light generated from the first light-emitting portion **121**, and the second metal layer **172** may be formed on the second light-emitting portion **122** to block the light generated from the second light-emitting portion **122**.

[0144] Meanwhile, each of the first metal layer **171** and the second metal layer **172** described above may be composed of a single layer or multiple layers. When each of the first metal layer **171**

and the second metal layer **172** is composed of as multiple layers, a lower layer may have an absorptive property to block light generated from below, and an upper layer may have a reflective property to reflect light generated from above. For example, Ag/Ni may correspond to the multiple layers. In addition, each of the first metal layer **171** and the second metal layer **172** may include an adhesive layer formed of Ti, Cr, Ni, or the like to improve adhesiveness. In addition, considering reflection/absorption, a thickness of each of the first metal layer **171** and the second metal layer **172** is preferably the minimum thickness to block 100% of light therebelow. This is because when the thickness is thick, there is a difficulty in a transparent conductive bonding and planarizing process.

[0145] In addition, each of the first bypass layer **181** and the second bypass layer **182** described above may be formed of an optically transparent and electrically conductive material and may be preferably formed of a material having low resistance and high transmittance characteristics. Such materials may include In₂O₃, SnO₂, ZnO, IZO, ITO, IGZO, and the like, but the present invention is not limited thereto.

[0146] Meanwhile, the plurality of LED stacks **200** disposed and arranged on the plurality of CMOS electrode pads **141** may be divided into preset units, and here, the preset units be pixel or subpixel units and may refer to a diameter (width) of the plurality of LED stacks **200**.

[0147] More specifically, the first light-emitting portion **121** may be etched and divided into first units, the second light-emitting portion **122** may be etched and divided into second units, and the third light-emitting portion **123** may be etched and divided into third units. Here, the first unit may be smaller than the second unit, and the second unit may be smaller than the third unit (the third light-emitting portion **123** may have a smaller diameter than the second light-emitting portion **122**, and the second light-emitting portion **122** may have a smaller diameter than the first light-emitting portion **121**). That is, a light-emitting area of the second LED stack **220** may be smaller than a light-emitting area of the first LED stack **210**, and a light-emitting area of the third LED stack **230** may be smaller than the light-emitting area of the second LED stack **220**, but the present invention is not limited thereto.

[0148] In addition, in the present invention, an operating voltage is generated differently for each of the plurality of LED stacks **200**. Specifically, in the first LED stack **210**, current flow into the third light-emitting portion **123** and the second light-emitting portion **122** is blocked so that a voltage (for example, 3 V) is applied to only one layer, i.e., the first light-emitting portion **121**, in the second LED stack **220**, current flow into the third light-emitting portion **123** is blocked, and the second light-emitting portion **122** and the first light-emitting portion **121** are connected in series so that a voltage (for example, 6 V) is applied thereto, and in the third LED stack **230**, the first to third light-emitting portions **121** to **123** are all connected in series so that a voltage (for example, 9 V) is applied thereto.

[0149] The mold portion **150** supports a vertically stacked LEDoS structure and is disposed to fill a space between the plurality of arranged LED stacks **200**.

[0150] The common electrode **160** is formed on the plurality of LED stacks **200** on which the mold portion **150** is formed. Similar to the ohmic contact electrode **124**, the common electrode **160** may be formed of a material that is transparent and conductive. When the common electrode **160** is an anode, a material of the common electrode **160** may include NiO, PtO, PdO, AgO₂, Au, Rh₂O₃, RuO₂, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO. When the common electrode **160** is a cathode, the material of the common electrode **160** may include TiN, CrN, VN, In₂O₃, SnO₂, ZnO, IZO, ITO, and IGZO.

[0151] In addition, a surface of the common electrode **160** may also be polished and smoothly planarized through MP or CMP.

[0152] Furthermore, although not shown, a protection layer may be additionally formed using a transparent organic material to protect the common electrode **160** from the atmospheric environment.

[0153] As described above, although all the components constituting embodiments disclosed herein were described as being combined or combined to operate as one, the present invention is not necessarily limited to these embodiments. That is, one or more of all the components may be selectively combined to operate as one without departing from the scope of the purpose of the present invention.

[0154] In addition, the terms “include,” “consist,” or “have” as described above mean that a corresponding component may be intrinsic, unless specifically stated otherwise, and it should be interpreted as including other components rather than excluding other components. All terms including technical or scientific terms have the same meanings as those commonly understood by those skilled in the art to which the present invention pertains, unless defined otherwise. Commonly used terms, such as terms defined in a dictionary, should be interpreted as being consistent with the contextual meaning of the related art and are not interpreted in an ideal or excessively formal meaning unless explicitly defined herein.

[0155] The above description is merely illustrative of the technical idea of the present invention, and those skilled in the art to which the present invention pertains may make various modifications and variations without departing from the essential characteristics of the present invention.

[0156] Accordingly, embodiments disclosed in the present invention are not intended to limit the technical idea of the present invention, but are for illustrative purposes, and the scope of the technical idea of the present invention is not limited by these embodiments. The spirit and scope of the present invention should be interpreted by the appended claims and encompass all equivalents falling within the scope of the appended claims.

Claims

1. A vertically stacked microdisplay panel that does not require a color filter, comprising: a back wafer having a plurality of complementary metal oxide semiconductor (CMOS) electrode pads arranged on an upper surface thereof; a plurality of light-emitting diode (LED) stacks in which a plurality of light-emitting portions and a plurality of bonding layers are vertically stacked on the back wafer and which are arranged on the plurality of CMOS electrode pads; and a common electrode formed on each of the plurality of LED stacks, wherein each of the plurality of LED stacks emits only light of a specific color by blocking light generated from at least one light-emitting portion of the plurality of light-emitting portions or forming a bypass layer along an outer surface of the light-emitting portion to divert a current so that the current does not flow into the light-emitting portion.
2. The vertically stacked microdisplay panel of claim 1, wherein the plurality of LED stacks include a first LED stack configured to emit only light having a first color, a second LED stack configured to emit only light having a second color, and a third LED stack configured to emit only light having a third color, and each of the first LED stack, the second LED stack, and the third LED stack includes a first light-emitting portion bonded onto the CMOS electrode pad through a first bonding layer to emit light having the first color, a second light-emitting portion bonded onto the first light-emitting portion through a second bonding layer to emit light having the second color, and a third light-emitting portion bonded onto the second light-emitting portion through a third bonding layer to emit light having the third color.
3. The vertically stacked microdisplay panel of claim 2, wherein the first LED stack emits only the light having the first color by forming the bypass layer along outer surfaces of the third light-emitting portion and the second light-emitting portion to divert a current so that the current does not flow into the third light-emitting portion and the second light-emitting portion, the second LED stack emits only the light having the second color by forming the bypass layer along the outer surface of the third light-emitting portion to divert a current so that the current does not flow into the third light-emitting portion and blocking light generated from the first light-emitting portion,

and the third LED stack emits only the light having the third color by blocking light generated from the second light-emitting portion and the first light-emitting portion.

4. The vertically stacked microdisplay panel of claim 3, wherein the second LED stack blocks the light generated from the first light-emitting portion through a metal layer formed on the first light-emitting portion, and the third LED stack blocks the light generated from the second light-emitting portion and the first light-emitting portion through the metal layer formed on each of the second light-emitting portion and the first light-emitting portion.

5. The vertically stacked microdisplay panel of claim 4, wherein the metal layer includes a lower layer which has an absorptive property to block light generated from below and an upper layer which has a reflective property to reflect light generated from above.

6. The vertically stacked microdisplay panel of claim 1, wherein the bypass layer is formed of a material that is optically transparent and electrically conductive.

7. The vertically stacked microdisplay panel of claim 1, wherein the bonding layer is formed of a ceramic material that is optically transparent and electrically conductive.

8. (canceled)

9. The vertically stacked microdisplay panel of claim 1, wherein an ohmic contact electrode is formed on at least one of an upper surface and a lower surface of each of the light-emitting portions.

10. The vertically stacked microdisplay panel of claim 9, wherein the ohmic contact electrode is formed of a material that is optically transparent and electrically conductive.

11. A method of manufacturing a vertically stacked microdisplay panel that does not require a color filter, the method comprising: a preparing operation of preparing a plurality of front wafers which include a support wafer and a light-emitting portion and emit light having different colors, and preparing a back wafer having a plurality of complementary metal oxide semiconductor (CMOS) electrode pads arranged on an upper surface thereof; a stacking operation of repeating a process of bonding the front wafer onto the back wafer through bonding layers and then removing the support wafer and vertically stacking the plurality of light-emitting portions and the bonding layers on the back wafer; an etching operation of etching and dividing the plurality of stacked light-emitting portions and bonding layers into preset units and arranging a plurality of light-emitting diode (LED) stacks on the plurality of CMOS electrode pads; and a forming operation of forming a common electrode on the plurality of LED stacks, wherein each of the plurality of LED stacks emits only light of a specific color by blocking light generated from at least one light-emitting portion of the plurality of light-emitting portions or forming a bypass layer along an outer surface of the light-emitting portion to divert a current so that the current does not flow into the light-emitting portion.

12. The method of claim 11, wherein the plurality of front wafers include a first front wafer including the support wafer and a first light-emitting portion, a second front wafer including the support wafer and a second light-emitting portion, and a third front wafer including the support wafer and a third light-emitting portion, and the plurality of LED stacks include a first LED stack configured to emit only light having a first color, a second LED stack configured to emit only light having a second color, and a third LED stack configured to emit only light having a third color.

13. The method of claim 12, wherein the stacking operation includes a first stacking operation of bonding the first front wafer onto the back wafer through a first bonding layer and then removing the support wafer to stack the first light-emitting portion on the back wafer, a second stacking operation of bonding the second front wafer onto the first light-emitting portion through a second bonding layer and then removing the support wafer to stack the second light-emitting portion on the first light-emitting portion, and a third stacking operation of bonding the third front wafer onto the second light-emitting portion through a third bonding layer and then removing the support wafer to stack the third light-emitting portion on the second light-emitting portion.

14. The method of claim 13, wherein, in the first stacking operation, after the support wafer is

removed, a metal layer is formed on a portion of the first light-emitting portion, in the second stacking operation, after the support wafer is removed, the metal layer is formed on a portion of the second light-emitting portion, the second LED stack blocks light generated from the first light-emitting portion through the metal layer formed on the first light-emitting portion, and the third LED stack blocks light generated from the second light-emitting portion and the first light-emitting portion through the metal layer formed on each of the second light-emitting portion and the first light-emitting portion.

15. The method of claim 14, wherein the metal layer includes a lower layer which has an absorptive property to block light generated from below and an upper layer which has a reflective property to reflect light generated from above.

16. The method of claim 13, wherein the etching operation includes a first etching operation of etching and dividing the third light-emitting portion and the third bonding layer into first units, a second etching operation of etching and dividing the second light-emitting portion and the second bonding layer into second units, and a third etching operation of etching and dividing the first light-emitting portion and the first bonding layer into third units.

17. The method of claim 16, wherein, in the first etching operation, after the third light-emitting portion and the third bonding layer are etched and divided into the first units, the bypass layer is formed along an outer surface of the third light-emitting portion at a portion in which the second LED stack is formed, in the second etching operation, after the second light-emitting portion and the first bonding layer are etched and divided into the second units, the bypass layer is formed along outer surfaces of the third light-emitting portion and the second light-emitting portion at a portion in which the first LED stack is formed, the first LED stack diverts a current through the bypass layer formed along the outer surfaces of the third light-emitting portion and the second light-emitting portion so that the current does not flow into the third light-emitting portion and the second light-emitting portion, and the second LED stack diverts a current through the bypass layer formed along the outer surface of the third light-emitting portion such that the current does not flow into the third light-emitting portion.

18. The method of claim 17, wherein the bypass layer is formed of a material that is optically transparent and electrically conductive.

19. The method of claim 11, wherein the bonding layer is formed of a ceramic material that is optically transparent and electrically conductive.

20. (canceled)

21. The method of claim 11, wherein an ohmic contact electrode is formed on at least one of an upper surface and a lower surface of each of the light-emitting portions.

22. The method of claim 21, wherein the ohmic contact electrode is formed of a material that is optically transparent and electrically conductive.
